Report of Diamond Drilling

on the

Mine Centre Gold Properties

Northwestern Ontario

Mining Claim K-3014618



Held by

Q-Gold (Ontario) Limited

2.37422

Prepared by Northwest Mineral Development Services

Kenora, Ontario March 8, 2007 Richard Beard, P.Eng

SUMMARY

During the months of March through May 2007, Q-Gold (Ontario) Limited drilled 21diamond drill holes on the Company's Mine Centre gold properties located in the Kenora Mining Division.

Nine of these holes were drilled on the Manhattan/Lucky Linda Group of claims to test two previously know gold veins, the Manhattan Vein and the Lucky Linda Vein. (see location plan for drill holes Q-07-16 and -17)

A series of six short "fan" holes from two drill locations were drilled on the Lucky Linda vein, an unexplored but extensive outcropping quartz vein in the Foley Complex. Extending on surface for over 1,000 metres, it is gold bearing at the surface, but of unknown depth. Two of these holes, as follows, are reported herein.

Q-07-16	K-3014618	101.00 m.
Q-07-17	K-3014618	63.00 m.

Although a number of zones of quartz veining up to 2.4 metres wide were penetrated in the Lucky Linda vein, no significant mineral assay values were encountered.

LOCATION AND ACCESS

Q-Gold's Mine Centre properties are situated in unorganized territory in Northwestern Ontario, approximately 65 kilometres east of Fort Frances, Ontario (Key Map).


The village of Mine Centre is located near the northern edge of the claim groups. All claims lie within NTS 52-C/10, C / 15 and C/16 map sheets. Highway 11 passes through the property, and the drill site and the numerous known mineral deposits and showings on the property can be easily accessed by the Shoal Lake Road, which takes off from highway 11 one kilometre east of the village of Mine Centre, and runs south the full length of the claim groups.

PROPERTY

Q-Gold's properties in the Mine Centre area consist of a large group of unpatented mining claims, leases and patents. All of the Company's mining claims, leases, and patents in this area are contiguous.

The property is described in detail in a previous Company report, "Report on the Northwestern Ontario Gold & Base Metal Properties, Mine Centre Area, Rainy River District, Held by Hexagon Gold (Ontario) Ltd." by Northwest Mineral Development Services, March 20, 2003.

Q-GOLD (ONTARIO) LTD.: MINE CENTRE PROJECT AREA Ontario, Canada



GENERAL GEOLOGY

The gold deposits of the Mine Centre gold camp largely occur within quartz veins intruded into a large unit of trondhjemite. This "Bad Vermilion tonalite/trondhjemite" is an elongate, sygmoid-shaped body oriented north-northeasterly in its central part, but deflected to the northeast at its northerly end and to the southwest at its southerly end. It is about 12 km long by 1.5 km at its widest point, in the vicinity of the Foley Mine, and tapers at each end. There is little compositional variation within the intrusion, which has been variously called a trondhjemite or a tonalite (compositionally equivalent terms): it is dominantly equigranular, plagioclase is the dominant feldspar, with subordinate potash feldspar, and quartz is commonly in the form of "eyes".

The current diamond drilling on the Manhattan/Lucky Linda Group was targeted to test for gold bearing quartz veins within the trondhjemite.

EXPLORATION SUMMARY

"(Previous) exploration and development work on the (Q-Gold's) mining properties in the Mine Centre area, took place during three periods: in the late 1800s, when most of the properties were first brought to production; in the 1920s and 1930s, when further development work and some production was undertaken on specific properties; and from 1940 to the present, when surface exploration was carried out sporadically throughout the area.

Most noteworthy of the more recent work were the following three programs. The first of these was a diamond drilling program carried out by Corporate Oil and Gas Ltd. in 1979-80, in a joint venture performed on the Foley and Ferguson properties, as well as the McKenzie-Gray (Nipigon) property. Forty-nine holes were drilled, totaling 11,119.7 ft. (Huston 1981)

In 1981 and 1982, Sherritt Gordon Mines Ltd. evaluated a large area that included the same properties plus the Decca, Manhattan, Lucky Coon and much of the area presently called the Bolen-McCormick claims. Their work included geological mapping and an extensive trenching and sampling program. A sampling program was also conducted on the Foley tailings (Sherritt Gordon Mines, 1982 and 1983).

In 1986-87, Orofino Resources Ltd. optioned a number of parcels of ground held by Jack Bolen, including most of the ground now held as the Bolen-McCormick claims. The company performed broad surveys over the Bad Vermilion tonalite/trondhjemite intrusion, but only drilled five short holes as follow-up."

In 2006, Q-Gold carried out an airborne geophysical survey that included the Nipigon claim group. This was followed up by ground geophysical surveys.

RESULTS

The six short "fan" holes drilled on the Lucky Linda Vein (see cross-sections for holes Q-07-16 and -17) were drilled to test an unexplored but extensive outcropping quartz vein in the Foley Complex. Extending on surface for over 1,000 metres, it is gold bearing at the surface, but of unknown depth. Although various zones of quartz veins and veining of up to 2.4 metres were intersected in holes Q-07-16 and Q-07-17, no significant mineral assay values were encountered.

Drill logs, assay sheets, a drill plan and drill section are attached as appendices.

The core (NQ2 (50.8mm)) is stored on the property.

SUMMARY OF COSTS

Diamond Drilling

George Downing Estate Drilling Ltd. \$ 16,603

Assaying SGS Canada Inc.

Report Preparation

Northwest Mineral Development Services \$ 1,000

> Total: \$ 17,603

REFERENCES

Beard, R.C. and Garratt, G.L. 1976. Gold Deposits of the Kenora - Fort Frances area, Districts of Kenora and Rainy River; Ontario Geological Survey, Mineral Deposits Circular 16, 46p.

Blackburn, C.E., Johns, G.W., Ayer, J. and Davis, D.W. 1991. Wabigoon Subprovince; *in* Geology of Ontario, Ontario Geological Survey, Special Volume 4, Part 1, p. 303-381.

Neilson, James N. & Bray, R.C.E., 1981. Feasibility of Small Scale Mining in Northwestern Ontario (parts of the Districts of Kenora, Rainy River and Thunder Bay; Ontario Geological Survey. Open File Report 5332 (Volumes 1 and 2).

Poulsen, K.H. 1984. The Geological Setting of Mineralization in the Mine Centre - Fort Frances area, District of Rainy River; Ontario Geological Survey. Open File Report 5512, 126p.

Poulsen, K.H. 2000. Precambrian Geology and Mineral Occurrences, Mine Centre - Fort Frances area; Ontario Geological Survey, Map 2525, scale 1:50,000.

Poulsen, K.H. 2000. Archean Metallogeny of the Mine Centre - Fort Frances area; Ontario Geological Survey, Report 266, 121p.

Stone, D., Halle, J. and Murphy, R. 1997a. Precambrian Geology, Mine Centre area; Ontario Geological Survey, Preliminary Map P.3372, scale 1:50 000.

Tanton, T.L. 1936. Mine Centre Area, Rainy River District;GeologicalSurvey of Canada, Map 334A, scale 1:31 680.

Williams, H.R. 1991. Quetico Subprovince; *in* Geology of Ontario, Ontario Geological Survey, Special Volume 4, Part 1, p. 383-403.

Wood, J., Dekker, J., Jansen, J.G., Keay, J.P. and Panagapko, D. 1980a. Mine Centre Area (west half), District of Rainy River; Ontario Geological Survey, Map P.2201, scale 1:15 840.

Wood, J., Dekker, J., Jansen, J.G., Keay, J.P. and Panagapko, D. 1980b. Mine Centre Area (east half), District of Rainy River; Ontario Geological Survey, Map P.2202, scale 1:15 840.

Author of Report

Richard Beard Northwest Mineral Development Services

Summer: Site 148, Comp. 9, RR #1 Kenora, ON, P9N 3W7

Winter: 4065 E. University Dr., #96

Mesa, AZ, USA, 85205

Supervisor of Work

Jack Bolen 521 Mowat Ave. Fort Frances, ON P9A 3M5

Submitted by Richard Beard, P.Eng. March 8, 2008

APPENDIX "A" – DRILL HOLE Q-07-16

Drill Logs, Plans & Sections

Drillhole Log

Q-Gold (Ontario) Ltd	1						Units Meters
Province/State	UTM East	Datum	Local Grid E	Azimuth Grid (°)	Length	Core Size	Date Started
Ontario	526966	NAD 83	650.00	58.00	101.00	NQ	05/09/2007
District	UTM North	UTM Zone	Local Grid N	Azimuth Astro. (°)	Collar Surve	ey Method	Date Completed
Kenora	5396342	15	0.00				05/11/2007
Grid/Property	UTM Elevation	Drill Contracto	r	Dip (°)	Logged By		i
A.O. A.	390.00	George Down	ng Estate	-45.00	Jack M. Bol	en, B.Sc.	
Claim No.	Pulsed	Geophysics C	ontractor	Casing Pulled	Casing	Plugged	Plug Depth
3014618		:			2.70		
Purpose			A Village	Core Storage			
Results				Comments			

Survey Tests

Lithology			Assays			Au	Ag	Cu
FROM TO			SAMPLE#	FROM	<u>то</u>	ppm_	ppm	
0.00 - 2.7		B <u>Overburden</u> rburden, casing.						
2.70 - 28.	Tror 40%	Trondhjemite (quartz porphyritic) adhjemite. Very coarse grained. Massive. Mottled red and green. Locally weakly sericitic. by 4-8 mm, gray quartz eyes. Localized minor fracturing.						
	6.80	Veinlets, 1-5 cm, pyrite, chalcopyrite						
10.00 -		Veinlets, 1-5 cm, pyrite, chalcopyrite						
11.90 -		QV Quartz Vein Veinlets, 1-5 cm, pyrite, chalcopyrite						
12.30 -		Veinlets, 1-5 cm, pyrite, chalcopyrite						
13.05 -	13.06	QV Quartz Vein Veinlets, 1-5 cm, pyrite, chalcopyrite						
Alteration:								
2.70 -	28.00	Sericitization Locally Weak, Silicification Eyes Moderate 40%, 4-8 mm, gray quartz eyes						
Structure:								
2.70 -	28.00	Fracture 0° to C/A Localized, minor						
28.00 - 41.	00 9 c	Trondhjemite (quartz porphyritic)						
	mot	dhjemite. Fine grained, 10-15%, gray quartz eyes. Fine grained, gray green matrix. 10%, led feldspar phenocrysts. Weak fracturing, often with black, hairline tourmaline cementing. 5-piotite/chlorite.						
Mineraliza	tion:							
28.00 -	41.00	Tourmaline Cemented Weak fracturing, often with black, hairline tourmaline cementing						
Alteration:								
28.00 -	41.00	Silicification Eyes Moderate, Biotization Weak, Chloritization Weak 10-15%, gray quartz eyes, fine grained, gray green matrix, 10% feldspar phenocrysts, mottled phenocrysts, 5-8% biotite/chlorite						
Structure:								
28.00 -	41.00	Fracture 0° to C/A Weak, often with black, hairline tourmaline cementing						

Lithology FROM TO	Assays SAMPLE#	EROM	то	Au ppm	Ag ppm	Cu ppm	
-	SAMPLE #	- KOIN	10	ppiii	ppiii	ppiii	
41.00 - 45.01 9c Trondhjemite (quartz porphyritic)							
Trondhjemite. Coarse grained. Dark red hematite staining. 5% chlorite clots after biotite.							
	85166	44.00	45.01	0.00	0.15		
Mineralization:							
44.00 - 45.01 Pyrite Trace							
Alteration:							
41.00 - 45.01 Hematization , Chloritization Clots Weak, Biotization Dark red hematite staining, 5% chlorite after pyrite							
44.00 - 45.01 Hematization							
Dark red trondhjemite							
45.01 - 46.60 QV Quartz Vein							
Quartz Vein. Ribboned. 1-3% combined pyrite, chalcopyrite, sphalerite, galena.							
45.01 - 46.60 QV Quartz Vein	85167	45.01	45.50	0.00	0.15		
Ribboned, combined pyrite, chalcopyrite, sphalerite, galena	85168	45.50	46.05	0.08	5.30		
45.02 - 45.50 QV Quartz Vein	85169	46.05	46.60				
50% veining, pyrite, sphalerite, galena							
45.50 - 46.05 QV Quartz Vein							
Well banded, combined pyrite, sphalerite, galena, chalcopyrite							
46.05 - 46.60 QV Quartz Vein							
Well banded, combined pyrite, sphalerite, galena, chalcopyrite, contacts at 58 to CA							
Mineralization:							
45.01 - 46.60 Pyrite 3.00%, Galena 3.00%, Sphalente 3.00%							
1-3% combined pyrite, chalcopyrite, sphalerite, galena, in quartz vein							
45.02 - 46.60 Chalcopyrite 3.00% 1-3% combined pyrite, chalcopyrite, sphalerite, galena, in quartz vein							
45.03 - 45.50 Pyrite Trace, Galena Trace, Sphalerite Trace							
45.50 - 46.05 Pyrite 3.00%, Galena 3.00%, Sphalerite 3.00%							
3% combined pyrite, chalcopyrite, sphalerite, galena, in quartz vein							
45.51 - 46.60 Chalcopyrite 3.00%							
3% combined pyrite, chalcopyrite, sphalerite, galena, in quartz vein							
Structure:							
45.01 - 45.50 0° to C/A Breccia							

Lithology FROM TO	Assays		70	Au	Ag	Cu
FROM 10	SAMPLE#	FROM	<u> </u>	ppm	ppm	ррт
46.60 - 53.35 9c Trondhjemite (quartz porphyritic)						
Trondhjemite. Massive. Sheared. 50%, very prominat, red quartz eyes, in a light green serimatrix. Microbrecciated.	citic					
50.60 - 51.60 QV Quartz Vein	85170	46.60	47.60	0.00	0.15	
5% veining	85171	47.60	48.60	0.00	0.15	
	85172	48.60	50.60	0.00	0.15	
	85173	50.60	51.60	0.00	0.15	
Alteration:						
46.60 - 53.35 Silicification Eyes Moderate, Sericitization Matrix 50%, very prominant, red quartz eyes, in a light green sericitic matrix						
46.61 - 50.60 Hematization Clasts Weak, Silicification Eyes Moderate, Sericitization Matrix Mottled green and red with 2% red hematite clots, 50%, blue quartz eyes, coarse						
grained						
Structure:						
46.60 - 53.35 0° to C/A Microbrecciated						
46.61 - 53.35 Shearing 0° to C/A						
50.60 - 51.60 Shearing 0° to C/A Weak						
53.35 - 101.00 9f Trondhjemite (15-25% mafics)						
Trondhjemite. Coarse grained. Biotitic. 35-40%, gray quartz eyes. 15-20%, up to 6 mm biotooks. Green, red and white feldspar matrix.	ite					
57.45 - 57.59 QTV Quartz Tourmaline Veln 35 to CA						
Alteration:						
53.35 - 101.00 Silicification Eyes Moderate, Biotization Moderate						
35-40%, gray quartz eyes, 15-20%, up to 6 mm biotite books, green, red and white feldspar matrix						
Structure:						
60.00 - 61.00 Shearing 0° to C/A Fine grained, weak						
68.52 - 68.92 Shearing 48° to C/A 10 cm						

PASSES SE

No. 2716 200

Sec. 35.

-4:2 100

 $\phi(x) = (x,y)$

.....

. . . .

of Page 466

وفروس · :(i) 3.02000 100

818 B

1 or other


أوؤوا وأر 5110 3----

A 100

4.00 14.34

2770





Oct 10, 2007

Date:

Certificate of Analysis

Work Order: 094279

To: c/o Hexagon Resources Inc.

121 East Birch Avenue,

Suita 508 FLAGSTAFF **ARIZONA 86001**

U.S.A.

the transfer

P.O. No.

RL28968

Project No.

DEFAULT

No. Of Semples

111

Date Submitted

Jul 25, 2007

Report Complises

Pages 1 to 4

(Inclusive of Cover Sheet)

Distribution of unused material:

Discard after 90 days: 111 Pulps

Cartified By :

Russ Calow, B.Sc., C.Chem. Vice President Global Geochemistry

ISO 17026 Accredited for Specific Tests. SCC No. 456

Report Footer:

LN.R. = Listed not received

I.S. = (neufficient Sample

A.B. Not applicable ⇒ No result

- Composition of this sample makes detection impossible by this method M after a result denotes ppb to ppm conversion, % denotes ppm to % conversion Methods marked with an asterial (e.g. TNAADSV) were subcontracted

Subject to SQS General Terms and Conditions

The date reported on this certificate of analysis represents the sample examined to SGS Minerale Services. Reproduction of this ensighing report. If full or in part, is prohibited without prior written approval.

SGB Canada loc.

Mineral Services 1985 Leslie Street Toronto ON MOS 2M3 (410) 445-5755 (410) 445-482 WWW.sps.ca



Final: 094279 Order: RL28968

Final: 094279 Order: R	L28968	
Element	Ag	
Mothed	AAS12E	
DieLin.	0.3	
Valls	G/I	
95134	₹0.3	(2-627-15
85135	<0.3	10-127-15
65138	- 0.4	W-27-11
65197	<0.3	
851 38	<0.3	;
96/139	<0.3	l. /
85140	≪0.3	Mark Programme and the second
85141	.∞. 0.9	
B5142	<0.3	The state of the s
85143	403	From the Commence of the Comme
95144	<0.3	<i>f</i>
B5145	40.3	
\$5146	1.6	
55147	<0.3	
25148	0.3	
	<0.9	I
95149		
85150	0.5	•
85151	0.4	1
85152	<0,3	
85153	◆0. 3	
85154	<0,3	
95155	40.3	· .
85156	<0.3	
85157	<0,3	<u> </u>
85158	<0.3	1
85159	<0.3	1
85 180	<0.3	:
85161	<0,3	
95162	<0.3	1
B5163	40,3	
65154	<0.3	1
25105	40.3	
\$5186	40.3	0-07-16
95167	10.0	
The second secon	5.3	
85170	<0.3	· /
85171	40.2	1
65172	<0.3	Ν.
86173	<0.8	
85174	€0.3	*
85175	40.9	^ -2-1-
85176	0.3	Q-07-17
)
85177	1.9	ماد
85178	0.4	
95179	<0.3	0-07-19
85180	<0.3	1
85181	<0.3	
95182	0.8	W

Page 3 of 4

1.12

The data reported on this certificate of Energies represents the sample submitted to SGS Minerals Services, Reproduction of this single-state approval.

SGS-Camela Inc. Milneral Services 1885 Looks Street Toronto ON M38 2019 445-6755 ((418) 445-6755 ((418) 445-6755

المغيسان. مخترية

Market of the Person Street, Square, 40 (1971)

4





particles with the CASTAL STATE CAST N. strice. A:505 1.8 62.7% 17.5-3. SE : 34 ** : ## (Fig. 2000 70. (45° v) 1577 B -W. Actio ting: in the $\mathbb{Z}_{q}^{p} V_{-1}$

× 8 × 5 STIDE 90 TE 1411 m

221-06 ra c 10,00 1

· 22.00). 1.00 (. E 344 1

Finalk 494279	Order: RL28968
,	

·: .	Final 494279 Order: R	L28968		
	- Missingt	AD		
, '';	Mediad	AAS12E		: <
•	Det Life. Liefts	0.3		. 6
	85183	<0.3	Q-07-19	.)
·	85184	-03		1.17
	86185	<0.3		
· · · * .	95186	<0.3	G-07-20	•
	85187	< 0.3	ا کیا	·' .
	05186	<0.3		
"	95189	<0.3		L
·	86190	<0.3	35189-91 ho Sindertal on dri But are in 30 G-07-21 Seguence	<i></i>
	10791	-0.3	S I wanted ou dri	11 109
	25184	-α8	The same in the	mala f cistor
	85195	<0.3	Bot Rice 101	
· .	95196	<0.3	G-07-21 8294000	leg.
	95197-	-0.3	.	÷.
	65198	<0,3		
- 100	85199	<0,3	The state of the s	f .
. vi.,	*Dob-82178	<0.3		erega ere
``•`;	Cup 62190	<0.3		
	*Dup-85102	0.7		1.4
	Dup 85114	<0.3		
	**Dub (86)34	<0.3		• •
	Dup 85146	1.8		Artist Application
	TOup 85158	<0.3 <0.3	/ \	
	'Dep 85171	<0,3	/ \	and the second
	7Dup.65163	<0.3	/ _	
. Z., ,	Dup 85197	₹0.3	1	
٠			•	1.71

٠., .

The date reported on this confliction of grayon represents the service submitted to SCS Minerale Services. Reproduction of this enablicing report, in full or in particular production of the enabling report, in full or in particular production of

1.0 . 4.

Mineral Services 1685 Leally Street Toronto ON MSB 2MS 4416) 445-6765 9416) 445-6765

DH 9-07-16



Certificate of Analysis

Work Order: RL29105

To: Q-GOLD (ONTARIO) LTD.

Attn: Jack Bolen 521 Mowat Avenue PO Box 358 Fort Frances ONTARIO P9A 3M5 Date: Sep 26, 2007

P.O. No.

Q GOLD

Project No.

90

No. Of Samples Date Submitted

Jul 10, 2007

Report Comprises

Pages 1 to 3

(Inclusive of Cover Sheet)

Certified By

Report Footer.

L.N.R. = Listed not received

.a. = Not applicable

1.S. = insufficient Sample

= No result

NF = Composition of this sample makes detection impossible by this method

M after a result denotes ppb to ppm conversion, % denotes ppm to % conversion

Subject to SGS General Terms and Conditions

The data reported on this certificate of analysis represents the sample submitted to SGS Minerals Services. Reproduction of this enalytical report, in full or in part, is prohibited without prior written approval.



- * * * * *

•	Fina	d : RL	29105					Page 3 of 3
Element	Au(M1)	Au(M2)	Au(M)	Au(P)	M150	P150	Au(Calc)	1.
Method	FAS30K	FAS30K	FAS30K	FAS30K	FAS30K	FAS30K	FAS30K	
Det.Lim.	0.001	0.001	0.001	0.001	0.01	0.01	0.001	
Units	OZ/T	QZЛ	OZ/T	ОZЛ	Grams	Grams	OZ/T	
86149	<0.001	<0.001	<0.001	0.001	961,00	104.35	<0.001	
85150	<0.001	<0.001	<0.001	<0.001	1499.00	226.23	<0.001	
85151	<0.001	<0.001	<0.001	<0.001	1592.00	193.84	<0.001	1 . 1
65152	<0.001	0.008	0.004	<0.001	1482.00	70.88	0.004	
85153	<0.001	0.002	0.001	0.004	1277.00	60.65	0.001	1 1
85154	0.070	0.057	0.064	0.780	1449.00	103.16	0.113	
85155	<0.001	<0.001	<0.001	0.003	1582.00	95.03	<0.001	
85156	<0.001	<0.001	<0.001	<0.001	1377.00	95.14	<0.001	[·
65157	<0.001	<0.001	<0.001	<0.001	2197.00	87.64	<0.001	,
85158	<0.001	<0.001	<0.001	0.002	1322.00	106.79	< 0.001	
85159	<0.001	<0.001	<0.001	0.001	1279.00	109.83	<0.001	· ·
85160	<0.001	<0.001	<0.001	<0.001	417.00	15.77	<0.001	. 1
85161	<0.001	<0.001	<0.001	<0.001	984.00	60.85	<0.001	· · · · · · · · · · · · · · · · · · ·
85152	0.002	0.008	0.004	0.020	1278.00	97.80	0.006	· •
65163	<0.001	<0.001	<0.001	0.004	1532.00	79.56	<0.001	
85164	<0.001	<0.001	<0.001	0.001	1356.00	86.84	<0.001	15
65165	<0.001	<0.001	<0.001	<0.001	1079.00	100.53		0.07-15
85166	<0.001	<0.001	<0.001	<0.001	1501.00	71.26	c0.000	Q-07-16
9CA-54	0.001	<0.001	0.007	<0.001	568.00	40.55	0.007	State of the state
	0.00	<0.001	0.003	0.094	1579.00	80.69	DEPOSIT	The same of the sa
		<0.001	<0.001	<0.001	1719.00	64.37	<0.001	1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1
65170	<0.001		0.002	<0.001	1641.00	75.02	0.002	-
85171	The state of the s		<0.001	<0.001	1576.00	116.06	<0.001	Francisco de la companya de la comp
55172	<0.001	<0.001	<0.001	0.001	1748.00	109.85	<0.001	and the state of t
85173			<0.001	<0.001	1678.00	64.92	<0.001	and the second and the second
85174	<0.001	<0.001					<0.001	C = 0 7 = 4/5
35175	<0.001	<0.001	<0.001	<0.001	1715.00	95.67		
85175	<0.001	0.006		0.014	1014.00	84.58	0.004	
85177	<0.001	<0.001	<0.001	<0.001	1250.00	89.13	<0.001	
85178	<0.001	<0.001	<0.001	0.007	477.00	20.58	<0.001	Q-07-19
85179	<0.001	<0.001	<0.001	<0.001	1414.00	19.20	<0.001	
85180	<0.001	<0.001	<0.001	<0.001	780.00	97.24	<0.001	
85181	<0.001	<0.001	<0.001	<0.001	1026.00	168.89	<0.001	
85182	0.007	<0,001	0.004	0.003	789.00	78.84	0.004	
65183	<0.001	<0.001	<0.001	<0.001	1431.00	228.81	<0.001	
85184	<0.001	<0.001	<0.001	<0.001	1133.00	225.71	<0.001	Q-07-21
65185	<0.001	<0.001	<0.001	<0.001	940.00	185,41	<0.001	
85186	<0.001	0.019	0.010	0.001	677.00	172.67	0.008	
85187	<0.001	<0.001	<0.001	0.040	1202.00	290.81	0.007	
85188	<0.001	<0.001	<0.001	<0.001	1398.00	193.37	<0.001	Secretary and a VIVAN
85189	<0.001	<0.001	<0.001	<0.001	1443.00	249.33	<0.001	Carrie San Ball Mary
85190	<0.001	<0.001	<0.001	<0.001	715.00	86.62	<0.001	
85191	< 0.001	<0.001	<0.001	<0.001	1421.00	149.22	<0.004	
*Dup 85101		-	-	-	-	-	***	A distance of the state of the
Dup 85125	1 1	-						
Dup 85149	+							
Dup 85174			-					

The data raported on this certificate of analysis represents the sample submitted to SGS Minerals Services. Reproduction of this enalytical report, in full or in part, is prohibited without prior written approval.

Drillhole Log

Q-Gold (Ontario) Ltd	d						Units Meters
Province/State	UTM East	Datum	Local Grid E	Azimuth Grid (°)	Length	Core Size	Date Started
Ontario	526966	NAD 83	650.00	58.00	63.00	NQ	05/11/2007
District	UTM North	UTM Zone	Local Grid N	Azimuth Astro. (°)	Collar Surve	ey Method	Date Completed
Kenora	5396342	15	0.00				05/12/2007
Grid/Property	UTM Elevation	Drill Contracto	or .	Dip (°)	Logged By		
	390.00	George Down	ing Estate	-58.00	Jack M. Bolen, B.Sc.		
Claim No.	Pulsed	Geophysics C	ontractor	Casing Pulled	Casing	Plugged	Plug Depth
3014618					3.00		
Purpose				Core Storage			
Results				Comments			

Survey Tests

	Assays			Au	Ag	Cu
ROM TO	SAMPLE #	FROM	<u>TO</u>	ppm	ppm	<i>ppm</i>
0.00 - 3.00 OVB <u>Overburden</u>						
Overburden, casing.						
3.00 - 47.00 9c Trondhjemite (quartz porphyritic)						
Trondhjemite. Coarse grained. Mottled color, gray, green red. Local, up to 10%, chloritic clots after biotite. 20-25%, gray quartz eyes. Feldspar matrix, locally weakly altered to sericite.						
16.90 - 16.92 QV Quartz Vein 2 cm, white						
32.80 - 33.00 13 <u>Dike Rocks</u> Pegmatite dike, pyrite						
Mineralization:						
32.80 - 33.00 Pyrite Trace In pegmatite dike						
Alteration:						
3.00 - 47.00 Chloritization Clots Moderate, Silicification Eyes Moderate, Sericitization Matrix Local, up to 10%, chloritic clots after biotite, 20-25%, gray quartz eyes, feldspar matrix, locally weakly altered to sericite						
47.00 - 53.25 9c <u>Trondhjemite (quartz porphyritic)</u>						
Trondhjemite. Coarse grained. Massive. Dark red, hematitic. 35-40%, gray quartz eyes with a red hematite rim.						
	85175	52.25	53.25	0.00	0.15	
Mineralization:						
52.25 - 53.25 Pyrite Trace						
Alteration:						
47.00 - 53.25 Hematization Rims Moderate, Silicification Eyes Moderate Dark red, hematitic, 35-40%, gray quartz eyes with a red hematite rim						
52.25 - 53.25 Hematization , Silicification Weak Red, hematitic trondhjemite, weak, local silicification						
53.25 - 54.95 QV <u>Quartz Vein</u>						
Quartz vein. Banded, pink and white.						
53.25 - 54.95 9c <u>Trondhjemite (quartz porphyritic)</u> 10%, trondhjemite clasts in quartz vein, pyrite, sphalerite, galena, agentite	85176 85177	53.25 54.00	54.00 54.95	0.19 0.14	0.30 0.30	
Mineralization:						

Lithology FROM TO		Assays SAMPLE#	FROM	то	Au ppm	Ag ppm	Cu ppm
53.25 - 54.95	Pyrite Trace , Sphalerite Trace , Galena Trace All mineralization within trondhjemite clasts, trace agentite						
54.95 - 56.70 9c Tron	Trondhjemite (quartz porphyritic) dhjemite. Coarse grained. Massive. Dark red, hematite stained.						
54.95 - 56.20	QV Quartz Vein 2-3 cm, 55 to CA	85178	54.95	56.20	0.01	0.40	
Alteration:							
54.95 - 56.70	Hematization Dark red, hematite stained						
56.70 - 63.00 9c	Trondhjemite (quartz porphyritic)						
	dhjemite. Very coarse grained. Massive. Pink. 20%, up to 6 mm chlorite/biotite grains, 10-, gray quartz eyes.						
Alteration:							
56.70 - 63.00	Chloritization Moderate, Biotization Moderate, Silicification Eyes Moderate 20%, up to 6 mm chlorite/biotite grains, 10-15%, gray quartz eyes						

\$ 第二位

No. 1992

-

N 15 15 25.45

. 4.

100 5. 0 $J^{(n)}/J_{\omega}/\epsilon.$ 1-13

8000

. .

ile is Same

 (\hat{m}^{*},\hat{m})

1500 Carro S = 2.

00100



Certificate of Analysis

Work Order: 694279

To: c/o Hexagon Resources Inc.

121 East Birch Avenue, Suite 508 FLAGSTAFF ARIZONA 86001 U.S.A.

Dete: Oct 10, 2007

P.O. No.

Project No. :

No. Of Samples Date Submitted

Report Comprises

111 Jul 25, 2007

RL28968

DEFAULT

Pages 1 to 4 (inclusive of Cover Sheet)

Distribution of unused material:

Discard after 90 days: 111 Pulps

Certified By:

Russ Calow, B.Sc., C.Chem. Vice President Global Geochemistry

ISO 17025 Accredited for Specific Tests. SCC No. 458

Report Footer:

L.N.R. = Listed not received

= inaufficient Sample

= Composition of this sample makes detaction impossible by this method M after a result disnotos ppb to pipa convention, % denotes ppm to % convention Mothade marked with an asteriak (e.g. "NAAOSV) were subcontracted

Subject to SGS General Terms and Conditions

The date reported on this certificate of enables represents the sample submitted to SSS Minerals Services. Reproduction of this enablical report, in full or in part, is prohibited without prior written approval.

Milneral Services 1995 Leelle Street Toronto ON M3B 2M3 6/16/4/6-5755 (416) 4/6-1152 www.sps.ce

SGS Canada Inc.





Page 3 of 4

	094279	Order:	RL28968

9287790107

Final: 094279 Order: R	L28968	
Element	Ag	
Method	AAS12E	
Dockhu.	0.3	
Units	ĠЛ	
95134	<0.3	1 1 -
65125	<0.8	
65138	0.4	,
96137	<0.3	3
05136	<0.3	. ,
95130	<0.3	ki 1
85140	<0.3	The Mark The Company of the Company
85141	v., 0.9	$\Gamma = \Gamma$
85142	<0.3	$I^{\sigma_{i}}$
85143	40.3	
85144	<0.3	la service
95145	<0.3	
85146	1.6	
85147	<0.9	
85148	0.3	
85149	≪0.3	!
95150	0.0	1
95151	0.4	
85152	<0.3	,
85153	<0.3	· ·
89154	<0.3	1
95155	<0.3	! !
95158	<0.3	:
85157 85158	<0.3	
85159	40.3	! [
85180	<0.3	,
96191	<0.3	1
85162	<0.3	,
85163	<0.3	i 1
85164	€0.3	
85165	€0.3	V
95166	40,3	0-07-14
95167	₹0.3	(A)
65166	5.3	/
85170	<0.3	/
85171	€0.3	/
25172	≪0.3	¥
95179	<0,3	
85174	16.0	1
85175	-0.8	Q-07-17
85126 · · · · · · · · · · · · · · · · · · ·	F (200)	1
	W 13	
200	.36	
86178		0-07 -19
85180 08178	<0.3	∽ ,
95181	<0.3	
86182	0.8	

www.co 4.11.0

The data reported on the certificate of analysis represents the sample submitted to SGS Minerals Services, Reproduction of the enarytical leads in the position of the enarytical leads in the sample submitted to SGS Minerals Services, Reproduction of the enarytical leads in the sample submitted to SGS Minerals Services, Reproduction of the enarytical leads in the sample submitted to SGS Minerals Services, Reproduction of the enarytical leads in the sample submitted to SGS Minerals Services, Reproduction of the enarytical leads in the sample submitted to SGS Minerals Services, Reproduction of the enarytical leads in the sample submitted to SGS Minerals Services, Reproduction of the enarytical leads in the sample submitted to SGS Minerals Services, Reproduction of the enarytical leads in the sample submitted to SGS Minerals Services, Reproduction of the enarytical leads in the sample submitted to SGS Minerals Services, Reproduction of the enarytical leads in the sample submitted to SGS Minerals Services, Reproduction of the enarytical leads in the sample submitted to SGS Minerals Services, Reproduction of the enarytical leads in the sample submitted to SGS Minerals Services, Reproduction of the enarytical leads in the sample submitted to SGS Minerals Services, Reproduction of the enarytical leads in the sample submitted to SGS Minerals Services, Reproduction of the sample submitted to SGS Minerals Services, Reproduction of the sample submitted to SGS Minerals Services, Reproduction of the sample submitted to SGS Minerals Services, Reproduction of the sample submitted to SGS Minerals Services, Reproduction of the sample submitted to SGS Minerals Services, Reproduction of the sample submitted to SGS Minerals Services, Reproduction of the sample submitted to SGS Minerals Services, Reproduction of the sample submitted to SGS Minerals Services, Reproduction of the sample submitted to SGS Minerals Services, Reproduction of the sample submitted to SGS Minerals Services (SGS Minerals Services). SGS Caracte Inc. | Allertal Services 1889 Leads Street Toronto ON M38 2M3 (415) 445-5755 (416) 465-4152 Versuspace

.... 13 $f(t) \neq$

. , .



DHQ-07-17

Certificate of Analysis

Work Order: RL29105

To: Q-GOLD (ONTARIO) LTD.

Attn: Jack Bolen 521 Mowat Avenue PO Box 358 Fort Frances ONTARIO P9A 3M5 Date: Sep 26, 2007

P.Q. No.

O GOLD

Project No.

No. Of Samples

90

Date Submitted

Jul 10, 2007 Pages 1 to 3

Report Comprises Page

(inclusive of Cover Sheet)

Certified By:

Report Footer.

L.N.R. = Listed not received

1.S. * Insufficient Sample

n.a. = Not applicable

= No result

"INF = Composition of this sample makes detection impossible by this method M after a result denotes ppb to ppm conversion, % denotes ppm to % conversion

Subject to SGS General Terms and Conditions

The data reported on this certificate of analysis represents the sample submitted to SGS Minerals Services. Reproduction of this analytical report, in full or in part, is prohibited without prior written approval.



Final: RL29105

Page 3 of 3

	1 1130	41 . ITL.	49 I UU					1 mgc 0 01 0
Element	Au(M1)	Au(M2)	Au(M)	Au(P) FAS30K	M150	P150	Au(Calc)	
Method	FAS30K	FAS30K	FAS30K			FAS30K	FAS30K	
Det Lim. Units	0.00f	0.001 OZ/T	0.001 OZ/11	0.001 OZ/T	0.01 Grams	0.01 Grams	0.001 OZ/T	
85149	<0.001	<0.001	<0.001	0.001	961.00	104.35	<0.001	
85150	<0.007	<0.001	<0.001	40.001	1499.00	226.23	<0.001	
85151	<0.001	<0.001	<0.001	< 0.001	1592.00	193.84	<0.001	
85152	<0.001	0.008	0.004	<0.001	1482.00	70.88	0.004	
85153	<0.001	0.002	0.001	0.004	1277.00	60.65	0.001	· /
85154	0.070	0,057	0.064	0.780	1449.00	103.15	0.113	
85155	<0.001	<0.001	<0.001	0.003	1582.00	95.03	<0.001	
85156	<0.001	<0.001	<0.001	<0.001	1377.00	95.14	<0.001	
85157	<0.001	<0,001	<0.001	<0.001	2197.00	87.84	<0.001	
85158	<0.001	<0.001	<0.001	0.002	1322.00	108.79	<0.001	\
85159	<0.001	<0.001	<0.001	0.001	1279.00	109.83	<0.001	1 1
85160	<0.001	<0.001	<0.001	<0.001	417.00	15.77	<0.001	\
85161	<0.001	<0.001	<0.001	<0.001	984.00	60.85	<0.001	
85162	0.002	0.006	0.004	0.020	1278.00	97.80	0.008	
88163	<0.001	<0.001	<0.001	0.004	1532.00	79.56	<0.001	
85164	<0.001	<0.001	<0.001	0.001	1356.00	86.84	<0.001	007-18
85165	<0.001	<0.001	<0.001	<0.001	1079.00	100.53	<0.001	7 -1/-
e51 6 6	<0.001	<0.001	<0.001 0.007	<0.001	1501.00	71.26 40.55	<0.001	
85167	0.014	<0.001	0.007		568.00	80.69	0.007	12
85168	0.006	<0.001 <0.001	<0.003	0.094 <0.001	1579.00 1719.00	64.37	0.008 <0.001	3-17
85170 85171	0.001	<0.001	0.002	<0.001	1641.00	75.02	0.002	
85172	<0.001	<0.001	<0.002	<0.001	1576.00	118.06	<0.002	A CALL OF THE STATE OF THE STAT
85173	<0.001	<0.001	<0.001	0.001	1748.00	109.85	<0.001	
85174	<0.001	<0.001	<0.001	<0.001	1678.00	64.92		
85175	<0.001	<0.001	< 0.001	<0.001	1715.00	95,67	<0.001	
82000	<0.001	0.006	0.003	0.014	1014.00	84,58	0.004	
654 <i>a</i> 7.**	<0.001	<0.001	<0.001	<0.001	1250.00	69.13	<0.001	
854784	<0.001	<0.001	<0.001	0.007	477.00	20,58	<0.004	
88179	<0.001	<0.001	<0.001	<0.001	1414.00	19.20	<0.001	Q-07-19
85180	<0.001	<0.001	<0.001	<0.001	780,00	97.24	<0.001	
85181	<0.001	<0.001	<0.001	<0.001	1028.00	166.89	<0.001	
85182	0.007	<0.001	0.004	0.003	789.00	78.84	0.004	
85183	<0.001	<0.001	<0.001	<0.001	1431.00	228.81	<0.001	
85184	<0.001	<0.001	<0.001	<0.001	1133,00	225,71	<0.001	Q-07-21
85185	<0.001	<0.001	<0.001	<0.001	940.00	185,41	<0.001	
95186	<0.001	0.019	0.010	0.001	677.00	172.67	0.008	
85187	<0.001	<0.001	<0.001	0.040	1262.00	290.81	0.007	
85188	<0.001	<d.001< td=""><td><0.001</td><td><0.001</td><td>1398.00</td><td>193,37</td><td><0.001</td><td>A A A A A A A A A A A A A A A A A A A</td></d.001<>	<0.001	<0.001	1398.00	193,37	<0.001	A A A A A A A A A A A A A A A A A A A
85189	<0.001	<0.001	<0.001	<0.001	1443.00	249.33	<0.001	ALTY (LUILA)
85190	<0.001	<0.001	<0.001	<0.001	715.00	86.62	<0.001	
85.191	<0.001	<0.001	<0.001	<0.001	1421.00	149.22	<0.004	
Dup 85101							-	A Charles of party of a 20 mm.
*Dup 86126	4							
*Dup 85149	1		-					
Dup 85174			-					

The data reported on this certificate of analysis represents the sample submitted to SGS Minerals Services. Reproduction of this analytical report, in full or inpart, is prohibited without prior written approval.

