



Opawica Explorations Inc.

Report

**Diamond Drilling
OPW-07-001 to 022**

**Matachewan Property
Powell Twp
Larder Lake Mining Division
Ontario**

Summary

Diamond drilling and assaying were completed on the Matachewan Property by Opawica Explorations Inc. in 2007. The objective of the drilling program was to explore for gold and base metal deposits within favourable geology near past producing mines, with most of the drilling targeting a number of recently outlined Quantec Titan 24 IP anomalies.

The Matachewan Property is comprised of 55 claims with an area of 926 hectares and is located a few kilometres WNW of the Town of Matachewan in central Powell Township, Northeastern Ontario. The south boundary of the Property lies a few hundred metres north of the past producing Young Davidson and Matachewan Consolidated gold mines which are presently being explored and developed by Northgate Minerals Corporation.

Most of the property is underlain by Temiskaming sedimentary rocks, with a belt of ultramafic to intermediate volcanic rocks along the north part of the property. Mafic to felsic intrusive rocks occur in both the sediments and volcanics.

Two mineral deposits – the Camking gold zone and the Walker copper zone – occur on the property, as well as a number of other gold and base metal showings.

Twenty two diamond drill holes (8,139 metres) were completed by Opawica in 2007 with 21 targeting new, untested, and widespread Quantec Titan 24 MT/DCIP anomalies, and 1 testing the Camking zone down plunge. Three thousand two hundred and fifty six core samples were assayed for gold and silver \pm copper, zinc, lead, molybdenum.

Twelve of the twenty one drill holes targeting Titan anomalies successfully tested the anomalies and hit increased sulphide mineralization in the targeted area, eight of the twenty one holes were partially or substantially dyked out by Matachewan diabase in the Titan target areas, one hole was abandoned before crossing the Titan target, and hole OPW-08-019 successfully tested the Camking zone at depth.

Eighteen of the holes contain assays above 0.2 g/t Au, with 6 holes having greater than 1.0 g/t Au. OPW-07-001 intersected 2.46 g/t Au over 2.3 metres, OPW-07-007 intersected 2.74 g/t Au over 2 metres, OPW-07-017 intersected 3.75 g/t Au over 1 metre and a wide section of anomalous Cu, 1.22 g/t Au over 1.2 metres, and 1.15 g/t Au over 1.0 metre, OPW-07-014 intersected 2.32 g/t Au over 1 metre and 1.78 g/t Au over 1 metre, OPW-07-018 intersected 1.15 g/t Au over 1 metre, and OPW-07-020 intersected 0.22 g/t Au and 0.333% Cu across 4.8 metres. Drill hole OPW-07-019 intersected Camking Zone mineralization below 400 metres with sections of hematized and silicified brecciated greywacke containing up to 15% pyrite, and assaying up to 2.21 g/t Au over 1 metre, with composite assays of 0.78 g/t Au over 14 metres and 0.59 g/t Au over 12 metres.

Table of Contents

Summary.....	i
Introduction.....	1
Property.....	1
Location and Access.....	2
Geology.....	3
Regional Geology.....	3
Property Geology.....	4
Exploration History.....	5
Current Work.....	6
Diamond Drilling and Assaying.....	6
Results.....	8
Conclusions.....	23
Recommendations.....	24
Exploration.....	24
Infill Drilling.....	25
References	26
Certificate of Qualifications.....	27

Illustration Index

Figure 1: Matachewan Property Claims.....	2
Figure 2: Location Plan.....	3
Figure 3: Geology Line 600 E - Line 600 W.....	4
Figure 4: Plan Map of Drill Holes and Titan IP Anomalies on Colour Magnetic Relief.....	7
Figure 5: Section Line 600 E – IP with DDH.....	9
Figure 6: Section Line 400 E - IP with DDH'S.....	9
Figure 7: Section Line 200 E - IP with DDH'S.....	10
Figure 8: Section Line 00 - IP with DDH.....	11
Figure 9: Section Line 200 W - IP with DDH'S.....	12
Figure 10: Section Line 400 W - IP with DDH'S.....	13
Figure 11: Section Line 600 W - IP with DDH'S.....	14

Appendices

Appendix A.....	
Core Logs.....	
Appendix B.....	
Assay Certificates.....	
Appendix C.....	
DDH Sections.....	
Maps.....	

Introduction

Diamond drilling and assaying were completed by Opawica Explorations Inc. during 2007 on the Matachewan Property in northeastern Ontario. Twenty two NQ sized diamond drill holes totalling 8,139 metres were drilled, with 21 drill holes testing Quantec MT/DCIP targets, and one testing the Camking zone down plunge. Three thousand two hundred and fifty six samples of sawn drill core were assayed for gold and silver \pm copper, zinc, lead, molybdenum.


Property

The Matachewan Property is comprised of 55 claims totalling 926 hectares within three claim blocks; a main block of 51 claims(865 hectares), and two 2 claim satellite blocks(35 and 26 hectares). The claims are listed in Table 1 and shown in Figure 1.

Table 1: List of Claims

Claim #	Claim #
MR5421	374240
MR37455	374241
MR37456	374242
L367899	374243
L367900	387779
L372901	387780
L372902	511486
L372903	511487
L372904	511488
L372905	511489
L372908	511490
L372909	523195 Satellite Block
L372910	523196 Satellite Block
L372911	523197 Satellite Block
L373507	523198 Satellite Block
340615	531566
340616	531567
374013	531568
374014	531613
374015	531614
374016	531615
374017	531815
374235	531816
374236	1206013
374237	1206306
374238	1206307
374239	3006742

Figure 2: Location Plan



Geology


Regional Geology

The Matachewan area is composed of Archean metavolcanic, metasedimentary and intrusive rocks which are part of the Abitibi Greenstone Belt. The Powell and Cairo Township area is underlain by tholeiitic flows of the Kinojevis group and calc-alkaline flows and pyroclastic rocks of the Blake River Group. Archean sedimentary rocks unconformably overlie the volcanic rocks. This volcano-sedimentary assemblage is intruded by Archean mafic sills, dikes and felsic intrusions. Proterozoic sedimentary rocks of the Huronian Group unconformably overlie the Archean rocks. The Larder Lake Fault Zone and the Galer Lake Fault strike easterly across the region.

Three past producing mines occur in Powell Township – The Young Davidson Mine and the Matachewan Consolidated Mine to the south of the Property and the Ryan Lake Mine to the north of the Property. The two mines to the south produced an aggregate of about a million ounces of gold mainly from quartz veined syenite porphyry (Young Davidson and Matachewan Consolidated) and also from quartz veined pyritic carbonatized rocks (Matachewan Consolidated). The Ryan Lake Mine to the north produced 5 million pounds of copper and some

molybdenum, gold, and silver from quartz veins and shear zones in mafic intrusive rocks and syenite porphyries.

Figure 3: Geology Line 600 E - Line 600 W



Property Geology

The southern two thirds of the property is mostly underlain by a tightly folded belt of grey to greenish grey sedimentary rocks of Timiskaming age consisting of conglomerate, greywacke and arkose with an east to northeast trend. Along the northern part of the property are east trending ultramafic to felsic volcanic rocks

of Keewatin age consisting of komatiite, basalt, dacite, and rhyolite. Intruding the sedimentary and volcanic rocks are dikes of mafic to ultramafic Haileyburian age serpentinite and diorite and also bodies and dikes of Algoman age syenite, syenite porphyry, mafic syenite and lamprophyre, all with a trend generally parallel to the volcanics and sediments. North trending Matachewan age mafic diabase dikes intruded the above assemblage of rocks. The Larder Lake Fault Zone is located south of the Property and the Galer Lake Fault is to the north.

Two significant mineral deposits exist on the Property, the Camking gold zone on claims L372911 and 374240, and the Walker copper zone on claim MR37455.

The Camking gold zone is an ENE striking, steeply NNW dipping (-70 to -75°) zone of brecciated, silicified and hematized sediments containing disseminated pyrite and having gold grades averaging 1 to 2 grams per tonne over wide intervals in drill core and has been drill tested over a strike length of 700 metres. A 175 metre long section of the zone on claim L372911, from grid 485W to 660W at 200N, has been drilled at 50 metre intervals to 100 metre depth – this 175 metre section averages 8 metres wide (true width) and to a depth of 100 metres contains 400,000 tonnes with an average grade of 1.5 grams Au per tonne.

The Walker copper zone also known as the “A” showing is a north trending zone along the contact of a syenite porphyry body and Timiskaming sedimentary rocks. Mineralization consists chiefly of chalcopyrite, some bornite, and ± gold and silver, and is associated with heavy quartz veining. Sampling across the zone has given average grades of 1.04% Cu across 32 feet. In 1965 a bulk sample of 2000 tons was milled at the Ryan Lake Mine with head grades averaging 0.607 % Cu.

Also widespread chalcopyrite mineralization occurs within syenite porphyry and Timiskaming sediments on claims MR37456, L373507, L372902, L372903. Composite copper grades of 0.04 to 0.077 % Cu across several hundred feet have been reported in drill holes and trenches.

Exploration History

Prospecting activity in the area increased in 1916 after Jake Davidson discovered gold near Davidson Creek, on ground that would become part of the Young Davidson Mine.

The Walker Cu “A” showing along the west boundary of claim MR37456 was trenched and chip sampled in 1955 with a composite grade of 1.04% Cu across 32 feet.

In 1956 Ethel Copper Mines Ltd drilled 12 diamond drill holes under and north and south of the Walker Cu “A” trench with Cu reported in 8 holes.

The Walker Cu “A” trench was enlarged in 1965 and 2,000 tons shipped and milled at the Ryan Lake Mine, with head grades averaging 0.607% Cu.

Majestic Construction Limited completed percussion drilling, trenching, stripping, diamond drilling and sampling in 1973 in the area of the Walker Cu “A” pit and to the west on claims MR37455, MR37456, 372902, 372093, 373507, and 367170 to evaluate the potential for a large tonnage Cu deposit in the syenite porphyries and adjacent sediments. Widespread cpy mineralization was

confirmed and in 1974 additional diamond drilling, percussion drilling, stripping and trenching were done with composite grades of .04 to .077% Cu over widths of several hundred feet reported.

In 1975 Campbell, Fiset, and King carried out stripping, blasting and sampling in a number of areas over several claims. The "CamKing" zone was discovered on claim L372311, was sampled with chip assays of 0.05 to 0.1 oz/ton Au across a width of several metres. The claims were optioned to Copper Lake Explorations. An IP survey was completed and diamond drilling of 571 feet in three holes at the CamKing zone gave composite assays to 0.10 oz/ton Au across 22 feet.

The Camking claims were optioned to Lacana Mining Corp in 1985. A program of line cutting, geophysics, mapping, chip sampling and diamond drilling of 6 holes (total of 2034 feet) gave a best composite assay in drill core of 0.05 oz/ton Au over 63 feet.

In 1995 Freewest Resources completed line cutting across 29 claims in the northwest and west part of the property, followed by ground geophysical surveys including 46 line kms of magnetic and VLV-EM surveying, and 18 line kms of IP surveying. Several anomalies were outlined and follow-up trenching tested some of the IP anomalies and the Camking zone. In 1996-97 diamond drilling along the Camking zone totalled 4,008 metres in 21 drill holes. The trenching and diamond drilling tested the Camking zone over a length of 700 metres across claims L372910, L372911, and 374240. The best intersections were on claim L372311 with composite assays of 1 to 2 grams of gold over several metres.

Sedex Mining Inc. completed line cutting and IP surveying on the east part of the Property in 1996-97. Strong IP anomalies were outlined followed by stripping and drilling 922 metres in 5 holes on claims 511490, 511489, 531816, and 1206300 with best assays of 1063 ppb and 1258 ppb over 1 metre core lengths.


Opawica completed power stripping in the winter of 2007 near the Walker Cu Pit, at the Camking Zone and at other areas across the property. Line cutting was completed and a Quantec Titan 24 IP survey was carried out over 7 lines at 200 metre line spacings, covering an area from the north claim boundary to the south boundary and including the Walker Cu Pit and Camking Zone and penetrating to a depth of 600 metres. Several high priority IP targets were delineated by the survey.

Current Work

Diamond Drilling and Assaying

Opawica Explorations Inc. completed a program of diamond drilling and assaying on the Matachewan Property in Powell Twp. Twenty two diamond drill holes totalling 8,139 metres were drilled from June 20, 2007 to September 14, 2007. Three thousand two hundred and fifty six core samples were assayed for gold and silver ± copper, lead, zinc, molybdenum from June 29 to October 22, 2007.

Figure 4: Plan Map of Drill Holes and Titan IP Anomalies on Colour Magnetic Relief



The work was supervised by the following Opawica personnel:

- Paul Antoniazzi of Kirkland Lake, Ontario
- Fred Sharpley of Kirkland Lake, Ontario
- Fred Kiernicki of Kirkland Lake, Ontario
- Terry Link of Kirkland Lake, Ontario

The drilling was carried out by Downing Drilling Limited of Grenville-Sur-La-Rouge, (Québec), using Longyear model LF70 diamond drills equipped with NQ drill tools. A Caterpillar D5 bulldozer or Caterpillar 320 excavator were used for site preparation and drill moves. The drills were operated 24 hours per day with

shifts of 12 hours and 2 men per shift per drill with Opawica personnel on site during the day to oversee the drilling. The core was transported to Opawica's core logging facilities in Matachewan, Ontario, where it was logged and sampled. Opawica geologist Fred Sharpley of Kirkland Lake logged the core and supervised the core sawing and sampling. Three thousand two hundred and fifty six core samples were assayed for gold and silver by fire assay. Opawica inserted standards every twenty samples, blanks and duplicates every twenty samples, to check the analytical accuracy. Assaying was completed by Swastika Laboratories Ltd., of Swastika, Ontario.

Of the twenty two drill holes completed, 21 targeted new, untested, widespread Quantec Titan 24 MT/DCIP anomalies, and 1 tested the Camking zone down plunge. The drill hole locations are shown in figure 4 above.

Twelve of the twenty one drill holes targeting Titan anomalies successfully tested the anomalies and hit increased sulphide mineralization in the target areas, eight of the twenty one holes were partially or substantially dyked out by Matachewan diabase in the Titan target areas, one hole was abandoned before crossing the Titan target, and hole OPW-08-019 successfully tested the Camking zone at depth.

Results

Eighteen of the holes had assays above 0.2 g/t Au, with 6 holes having greater than 1.0 g/t Au.

Three of the ten drill holes along the Walker Trend in the southern part of the property had intersections greater than 1 gram per ton; OPW-07-001 intersected 2.46 g/t Au over 2.3 metres in conglomerate, OPW-07-007 intersected 2.74 g/t Au over 2 metres in siltstone, OPW-07-018 intersected 1.15 g/t Au over 1 metre in conglomerate, and OPW-07-020 intersected 0.22 g/t Au and 0.333% Cu across 4.8 metres in siltstone.

In the central part of the property along the East Lake Trend two of four drill holes had intersections above 1.0 g/t; OPW-07-017 intersected 3.75 g/t Au and 22.8 g/t Ag over 1 metre in syenite porphyry, a wide section of anomalous Cu, 1.22 g/t Au over 1.2 metres in feldspar porphyry, and 1.15 g/t Au over 1.0 metre in conglomerate, and OPW-07-014 intersected 2.32 g/t Au over 1 metre in conglomerate and 1.78 g/t Au and 6.6 g/t Ag in feldspar porphyry.


In the northern part of the property along the Camking Trend, drill hole OPW-07-019 intersected Camking Zone mineralization below 400 metres with sections of hematized and silicified brecciated greywacke containing up to 15% pyrite, and assaying up to 2.21 g/t Au over 1 metre, with composite assays of 0.78 g/t Au over 14 metres and 0.59 g/t Au over 12 metres.

Sections of Lines 6E, 4E, 2E, 00, 2W, 4W, and 6W with drill holes and IP targets are shown in Figures 5 to 11 below and descriptions of drill holes follow each figure. Following the Section figures are 2 tables, Table 2 : Drill Hole Locations and Table 3: Assays > 0.1 g/t Au.

Drill hole logs with assays are included in Appendix A. Assay certificates are included in Appendix B. Diamond drill hole sections showing drill holes, rock

types, and Au bar graphs are included in Appendix C as well as plan maps showing drill hole locations.

Figure 5: Section Line 600 E – IP with DDH



Drill hole: OPW-07-001

Walker Trend

Collar: line 600E; station 1600S; azimuth 330; dip -65; length 600 m

Target: Titan 6E-C: priority 1; deep, broad IP; DC res low; MT res low


Lithology: conglomerate, siltstone, greywacke, lamprophyre, gabbro, quartz feldspar porphyry, syenite

Mineralization: pyrite through most of core; 1 to 10 %, high % py at IP anomaly

Assays: 28 samples > 0.1 to high of 3.41 g/t Au; 2.46 g/t Au(2.3 m)562 to 564.3 m

Comments: From 419 to 497 m porphyritic syenite, light pink with average of 5 % pyrite, quartz carbonate veining. IP anomaly corresponds with increased pyrite. Best gold assays at lower edge of IP anomaly.

Figure 6: Section Line 400 E - IP with DDH'S



Drill hole: OPW-07-002 Walker Trend

Collar: line 400E; station 1645S; azimuth 330; dip -55; length 201 m

Target: Titan 4E-B: priority 4; shallow, sharp IP; DC res low; MT res high

Lithology: conglomerate, diorite, siltstone

Mineralization: pyrite through most of core; 1 to 5 % pyrite; 2 to 5% pyrite through IP anomaly

Assays: 17 samples >0.1 to high of 0.81 g/t Au

Comments: Alteration zone from 36 to 119 m, medium to strong sericite-chlorite, 3 to 5% pyrite. IP anomaly corresponds with pyrite anomaly.

Drill hole: OPW-07-004 Walker Trend

Collar: line 400E; station 1500S; azimuth 330; dip -60; length 300 m

Target 1: Titan 4E-C: priority 3; shallow, sharp IP; DC res low; MT res low

Target 2: Titan 4E-E: priority 1; deep, broad IP; DC res contrast; MT res low

Lithology: siltstone, lamprophyre, diabase, conglomerate, syenite, greywacke, diorite, gabbro

Mineralization: pyrite – 1 to 5%; 1 to 5% py through IP anomaly

Assays: 21 samples > 0.1 to high of 0.45 g/t Au

Comments: Alteration from 356 to 367 m, strong hematite alteration, 3 to 5% py. Alteration from 367 to 388 m, strong sericite alteration, 3 to 5% py.

Drill hole: OPW-07-005 Walker Trend

Collar: line 400E; station 1350S; azimuth 330; dip -65; length 201 m

Target: Titan 4E-D: priority 2; shallow, strong IP; DC res high; MT res low


Lithology: greywacke, diorite, diabase

Mineralization: pyrite – nil to 8%; 2 to 8% py through IP anomaly

Assays: 1 sample > 0.1 g/t Au; 0.21 g/t Au (1 m)

Comments: IP anomaly corresponds with higher pyrite content.

Figure 7: Section Line 200 E - IP with DDH'S

**Drill hole: OPW-07-007 Walker Trend**

Collar: line 200 E ; station 1540S; azimuth 330; dip -50; length 201 m

Target: Titan 2E-B: priority 2; shallow IP; DC res low; MT res contrast

Lithology: diabase, greywacke, mafic dyke, siltstone

Mineralization: pyrite – 1 to 6%; 2 to 6% py within IP anomaly

Assays: 7 samples > 0.1 to high of 3.1 g/t Au; 2.74 g/t Au (2 m) 173.0 to 175.0 m

Comments: Alteration zone from 64 to 104 m, moderate to strong quartz-sericite, 3 to 5% py, green carbonate fragments. IP anomaly is coincident with pyrite mineralization increase.

Drill hole: OPW-07-008 Walker Trend

Collar: line 200E; station 1340S; azimuth 330; dip -50; length 201 m

Target: Titan 2E-C: priority 1; shallow, strong IP; DC res low; MT res low


Lithology: greywacke, diabase, feldspar porphyry, siltstone

Mineralization: pyrite – 1 to 5%; 3 to 5% py within IP anomaly

Assays: 0 samples > 0.1 g/t Au

Comments: Diabase from 120 to 201 m, dyked out lower edge of IP anomaly.

Figure 8: Section Line 00 - IP with DDH



Drill hole: OPW-07-020 Walker Trend

Collar: line 00; station 1550S; azimuth 330; dip -50; length 300 m

Target: Titan 0-B: priority 1; shallow/sharp, strong IP; DC res low; MT res low


Lithology: conglomerate, feldspar porphyry, mafic dyke, siltstone, diabase

Mineralization: pyrite – nil to 15%, blebs of chalcopyrite from 34 to 39 m

Assays: 11 samples > 0.1 to high of 0.45 g/t Au; 6 samples > 0.1% to high of 0.534 % Cu; 0.22 g/t Au and 0.333 % Cu (4.8 m) 34.4 to 39.2 m

Comments: Diabase totalling 187 metres in several sections, dyked out 2/3 of IP anomaly. Alteration zone from 110 to 143 m, strong sericite, minor green carbonate, 5 to 15% py.

Figure 9: Section Line 200 W - IP with DDH'S

**Drill hole: OPW-07-009 Camking Trend**

Collar: line 200W; station 305N; azimuth 330; dip -45; length 150 m

Target: Titan 2W-H

Lithology: greywacke, conglomerate, talc-chlorite schist, syenite porphyry

Mineralization: pyrite – nil to 1%; 1% pyrite at IP anomaly

Assays: 4 samples > 0.1 to high of 0.46 g/t Au; 0.46 g/t Au (0.5 m) 43.0 to 43.5 m

Comments: Talc-chlorite schist from 76 to 147 m, strongly sheared with numerous qz-carb veins. IP anomaly corresponds with higher pyrite section.

Drill hole: OPW-07-011 Camking Trend

Collar: line 200W; station 190N; azimuth 150; dip -60; length 351 m

Target: Titan 2W-G: priority 4; shallow IP; DC res high; MT low

Lithology: siltstone, lamprophyre, argillite, feldspar porphyry, diorite

Mineralization: pyrite – nil to 2%; 1 to 2% pyrite at IP anomaly

Assays: 0 samples > 0.1 g/t Au

Comments: IP anomaly coincident with increased pyrite section.

Drill hole: OPW-07-016 East Lake Trend

Collar: line 200W; station 410S; azimuth 150; dip -60; length 300 m

Target: Titan 2W-E: priority 4; shallow IP; DC weak res low; edge of MT


Lithology: greywacke, conglomerate, diabase

Mineralization: pyrite – nil to 3%; 1 to 3% py through IP anomaly

Assays: 16 samples > 0.1 to high of 0.9 g/t Au; 0.38 g/t Au (6.0 m) 61.0 to 67.0 m

Comments: Diabase from 234 to 300 m, lower edge of IP anomaly dyked out.

Figure 10: Section Line 400 W - IP with DDH'S

**Drill hole: OPW-07-003 Camking Trend**

Collar: line 400W; station 030S; azimuth 150; dip -60; length 597 m

Target: Titan 4W-D: priority 3; deep/broad IP; DC res high; MT res high

Lithology: siltstone, feldspar porphyry, greywacke, mafic dyke, ultramafic dyke, conglomerate, diabase

Mineralization: pyrite – nil to 5%; 1 to 5% pyrite through lower ½ of IP anomaly

Assays: 22 samples > 0.1 to high of 0.94 g/t Au; 1129.3 g/t Ag (1.0 m) 469.0 to 470.0 m

Comments: Diabase in bottom of hole, dyked out lower edge of IP anomaly.

Drill hole: OPW-07-013 Camking Trend

Collar: line 400W; station 325N; azimuth 150; dip -57; length 252 m

Target: Titan 4W-E: priority 2; shallow IP; DC res high; MT res low

Lithology: siltstone, greywacke, argillite, diorite, feldspar porphyry

Mineralization: pyrite – nil to 3%; sections of 1 to 3% py through IP anomaly

Assays: 17 samples > 0.1 to high of 0.47 g/t Au; 0.47 g/t Au (1 m) 151.0 to 152.0 m

Comments: IP anomaly explained by 1 to 3% pyrite sections.

Drill hole: OPW-07-017 East Lake Trend

Collar: line 400W; station 970S; azimuth 330; dip -50; length 498 m

Target 1: Titan 4W-B: priority 2; shallow IP; DC res high; MT res high

Target 2: Titan 4W-C: priority 2; broad IP; DC res high; MT res low

Lithology: conglomerate, lamprophyre, syenite porphyry, feldspar porphyry, greywacke, diabase

Mineralization: pyrite – nil to 5%; magnetite – 5 to 10% from 106 to 134 m; chalcopyrite – blebs, seams, and specks from 58 to 172 m

Assays: 19 samples > 0.1 to high of 3.75 g/t Au; 33 samples > 0.1% Cu to high of 0.25% Cu; 3.75 g/t Au and 22.8 g/t Ag (1 m) 79.0 to 80.0 m

Comments: Hematized sections at 58 to 86 m and 150 to 161 m. IP anomalies correspond with increase in pyrite, magnetite, and chalcopyrite.

Drill hole: OPW-07-021 Walker Trend

Collar: line 394W; station 1515S; azimuth 330; dip -70; length 702 m


Target: Titan 4W-A: priority 2; deep/broad IP; DC res high; MT res high
 Lithology: conglomerate, greywacke, mafic dyke, diabase, siltstone, feldspar porphyry

Mineralization: pyrite – nil to 3%

Assays: 10 samples > 0.1 to high of 0.33 g/t Au; 1 sample > 0.1% Cu (0.26%)

Comments: Diabase at 140 to 186 m, 203 to 521 m, and 533 to 542 m; 2/3 of IP anomaly dyked out.

Figure 11: Section Line 600 W - IP with DDH'S



Drill hole: OPW-07-006 Camking Trend

Collar: line 534W; station 00; azimuth 150; dip -65; length 432 m

Target: Titan 6W-F: priority 1; deep/broad IP; DC res high; MT res edge

Lithology: diabase, greywacke, mafic dyke, syenite, feldspar porphyry

Mineralization: pyrite – nil to 5%; 2 to 4% py in bottom section of hole at top edge of IP anomaly

Assays: 21 samples > 0.1 to high of 0.62 g/t Au; 0.62 g/t Au(1 m) 178.0 to 179.0 m

Comments: Hole abandoned before crossing IP anomaly, core barrel seized and left in hole. Anomalous Au in samples at end of hole.

Drill hole: OPW-07-010 Camking Trend

Collar: line 600W; station 230S; azimuth 150; dip -50; length 201 m

Target: Titan 6W-E: priority 2; shallow/sharp IP; DC res high; MT res low

Lithology: siltstone, greywacke, syenite, lamprophyre

Mineralization: pyrite – nil to 3%; pyrrhotite – 3 to 5% from 82 to 97 m

Assays: 15 samples > 0.1 to high of 0.73 g/t Au; 0.73 g/t Au(1 m) 170.0 to 171.0 m

Comments: IP anomaly corresponds with increased pyrite and pyrrhotite.

Anomalous Au in syenite and lamprophyre at lower edge of IP.

Drill hole: OPW-07-012 East Lake Trend

Collar: line 600W; station 430S; azimuth 150; dip -55; length 300 m

Target: Titan 6W-D: priority 2; shallow/sharp IP; DC res high; MT res edge

Lithology: diabase, conglomerate, syenite

Mineralization: pyrite – nil to 5%

Assays: 3 samples > 0.1 to high of 0.15 g/t Au

Comments: Diabase from 1 to 162 m, dyked out 2/3 of IP anomaly.

Drill hole: OPW-07-014 East Lake Trend

Collar: line 600W; station 800S; azimuth 150; dip -70; length 300 m

Target: Titan 6W-C: priority 1; shallow/sharp IP; DC res edge; MT res correlation

Lithology: conglomerate, greywacke, feldspar porphyry, lamprophyre, syenite porphyry

Mineralization: pyrite – nil to 5%; trace and rare bleb of chalcopyrite; disseminated magnetite in some conglomerate sections

Assays: 20 samples > 0.1 to high of 2.32 g/t Au; 2.32 g/t Au(1 m) 182.0 to 183.0 m; 2 samples > 0.1% to 0.315% Cu

Comments: IP anomaly corresponds with 1 to 5% pyrite and magnetite.

Drill hole: OPW-07-015 Camking Trend

Collar: line 600W; station 295N; azimuth 330; dip -60; length 201 m

Target: Titan 6W-G: priority 1; shallow IP; DC res low; MT res contrast

Lithology: diabase, mafic volcanic or greywacke, greywacke

Mineralization: pyrite – nil to 3%

Assays: 1 sample > 0.1 g/t Au (0.14 g/t)

Comments: Diabase at 4 to 50 m, 80 to 99 m, 102 to 134, IP anomaly substantially dyked out.

Drill hole: OPW-07-018 Walker Trend

Collar: line 600W; station 1300S; azimuth 330; dip -50; length 300 m

Target: Titan 6W-B: priority 3; shallow/broad IP; DC res high; MT res low

Lithology: siltstone, feldspar porphyry, argillite, conglomerate, mafic dyke

Mineralization: pyrite – nil to 3%

Assays: 11 samples > 0.1 to high of 1.15 g/t Au; 1.15 g/t Au(1 m) 210.0 to 211.0 m

Comments: IP anomaly corresponds with 1 to 3% pyrite.

Drill hole: OPW-07-022 Walker Trend

Collar: line 586W; station 1737S; azimuth 330; dip -60; length 651 m

Target: Titan 6W-A: priority 2; deep/broad IP; DC res high; MT res edge

Lithology: conglomerate, diabase, syenite, feldspar porphyry

Mineralization: pyrite – nil to 30%

Assays: 7 samples > 0.1 to high of 0.55 g/t Au; 0.49 g/t Au(2 m) 24.0 to 26.0 m

Comments: Alteration zone from 512 to 606 m, strong to weak sericite, silicified, 1 to 30% pyrite disseminations to stringers. Diabase dykes total 334 metres, 50% of IP anomaly dyked out.

Drill hole: OPW-07-019 Camking Zone – Camking Trend

Collar: line 850W; station 500N; azimuth 150; dip -65; length 600 m

Target: CamKing Zone – down plunge

Lithology: diabase, greywacke, argillite, feldspar porphyry, siltstone, ultramafic dyke, lamprophyre

Mineralization: pyrite – nil to 15%

Assays: 45 samples > 0.1 to high of 2.21 g/t Au; 0.78 g/t Au(14 m) 436.0 to 450.0 m; 0.59 g/t Au(12 m) 511.0 to 523.0 m

Comments: Camking zone penetrated – zones of weak to strong hematite alteration, silicified, brecciated, and with 1 to 15 % pyrite occur below 400 metres in OPW-07-019 and are usually Au enriched.

Table 2: Drill Hole Locations

Hole No.	Local Grid		UTM Zone 17 Nad 83		Dip	Az	Length (m)
	E	N	E	N			
OPW-07-001	600E	1600S	523073	5311704	-65	330	600
OPW-07-002	400E	1645S	522948	5311612	-55	330	201
OPW-07-003	400W	030S	521454	5312600	-60	150	597
OPW-07-004	400E	1500S	522879	5311733	-60	330	600
OPW-07-005	400E	1350S	522799	5311863	-65	330	201
OPW-07-006	534W	0	521329	5312566	-65	150	432
OPW-07-007	200E	1540S	522717	5311594	-50	330	201
OPW-07-008	200E	1340S	522625	5311771	-50	330	201
OPW-07-009	200W	305N	521475	5312998	-45	330	150
OPW-07-010	600W	230S	521383	5312327	-50	150	201
OPW-07-011	200W	190N	521529	5312896	-60	150	351
OPW-07-012	600W	430S	521478	5312174	-55	150	300
OPW-07-013	400W	325N	521288	5312918	-57	150	252
OPW-07-014	600W	800S	521657	5311835	-70	150	300
OPW-07-015	600W	295N	521129	5312796	-60	330	201
OPW-07-016	200W	410S	521820	5312371	-60	150	300
OPW-07-017	400W	970S	521912	5311782	-50	330	498
OPW-07-018	600W	1300S	521948	5311401	-50	330	300
OPW-07-019	850W	500N	520804	5312849	-65	150	600
OPW-07-020	0	1550S	522569	5311483	-50	330	300
OPW-07-021	394W	1515S	522170	5311303	-70	330	702
OPW-07-022	586W	1737S	522221	5311014	-60	330	651

Table 3: Assays > 0.1 g/t Au

Hole No.	Sample#	% Sul	From	To (m)	Width	Au g/t	Ag g/t	Cu %
OPW-07-001	34036	1	55.0	56.0	1.0	0.14	0.1	
OPW-07-001	34139	1	143.0	144.0	1.0	0.43	0.1	
OPW-07-001	34147	1	149.0	150.0	1.0	0.20	0.1	
OPW-07-001	34187	3	182.0	183.0	1.0	0.10	1.3	
OPW-07-001	34233	3	221.0	222.0	1.0	0.14	0.1	
OPW-07-001	34255	4	240.0	241.0	1.0	0.14	0.1	
OPW-07-001	34256	3	241.0	242.0	1.0	0.18	0.1	

Hole No.	Sample#	% Sul	From	To (m)	Width	Au g/t	Ag g/t	Cu %
OPW-07-001	34259	4	244.0	245.0	1.0	0.45	0.8	
OPW-07-001	34357	3	326.0	327.0	1.0	0.23	0.8	
OPW-07-001	34358	5	327.0	328.0	1.0	0.60	0.6	
OPW-07-001	34359	4	328.0	329.0	1.0	0.21	0.4	
OPW-07-001	34396	5	356.0	356.5	0.4	0.14	0.1	
OPW-07-001	34534	5	472.0	473.0	1.0	0.12	0.1	
OPW-07-001	34535	5	473.0	474.0	1.0	0.10	0.1	
OPW-07-001	34538	5	476.0	477.0	1.0	0.11	0.1	
OPW-07-001	34576	2	508.0	509.0	1.0	0.53	0.1	0.004
OPW-07-001	34595	2	524.0	525.0	1.0	0.35	0.1	0.058
OPW-07-001	34596	2	525.0	526.0	1.0	0.10	0.2	0.078
OPW-07-001	34615	2	541.0	542.0	1.0	0.23	0.1	0.044
OPW-07-001	34632	2	555.0	556.0	1.0	0.16	0.1	0.016
OPW-07-001	34634	2	557.0	558.0	1.0	0.35	0.1	0.055
OPW-07-001	34635	2	558.0	559.0	1.0	0.33	0.1	0.057
OPW-07-001	34636	2	559.0	560.0	1.0	0.13	0.1	0.046
OPW-07-001	34637	2	560.0	561.0	1.0	0.47	0.1	0.055
OPW-07-001	34638	3	561.0	562.0	1.0	0.26	0.1	0.033
OPW-07-001	34641	3	562.0	563.0	1.0	1.28	0.2	0.031
OPW-07-001	34642	3	563.0	564.3	1.3	3.41	0.6	0.067
OPW-07-001	Composite		562.0	564.3	2.3	2.46		
OPW-07-001	34668		586.0	587.0	1.0	0.12	0.2	
OPW-07-002	34687	3	6.0	7.0	1.0	0.19	0.3	0.009
OPW-07-002	34688	3	7.0	8.0	1.0	0.47	1.0	0.030
OPW-07-002	34689	3	8.0	9.0	1.0	0.81	1.6	0.036
OPW-07-002	34700	2	18.0	19.0	1.0	0.13	0.2	0.016
OPW-07-002	34708	1	24.0	25.0	1.0	0.04	9.2	0.053
OPW-07-002	34717	2	32.0	33.0	1.0	0.13	0.3	0.000
OPW-07-002	34727	3	40.0	41.0	1.0	0.11	1.0	0.015
OPW-07-002	34736	5	48.0	49.0	1.0	0.08	3.2	0.021
OPW-07-002	34746	5	56.0	57.0	1.0	0.10	1.1	0.009
OPW-07-002	34751	3	61.0	62.0	1.0	0.20	0.5	0.036
OPW-07-002	34752	3	62.0	63.0	1.0	0.18	0.9	0.018
OPW-07-002	34760	3	69.0	70.0	1.0	0.21	1.1	0.004
OPW-07-002	34765	5	72.0	73.0	1.0	0.11	1.0	0.007
OPW-07-002	34777	5	83.0	84.0	1.0	0.28	0.5	0.023
OPW-07-002	34778	5	84.0	85.0	1.0	0.10	0.8	0.008
OPW-07-002	34785	5	89.0	90.0	1.0	0.36	0.4	0.007
OPW-07-002	34786	5	90.0	91.0	1.0	0.11	0.5	0.009
OPW-07-002	34838	2	135.0	136.0	1.0	0.03	1.4	0.201
OPW-07-003	37180	2	8.0	8.6	0.6	0.14	0.7	
OPW-07-003	37181		8.6	9.3	0.7	0.29	0.8	
OPW-07-003	37183		10.0	11.0	1.0	0.12	0.3	
OPW-07-003	37184		11.0	12.0	1.0	0.12	0.1	
OPW-07-003	37195		21.0	22.0	1.0	0.10	0.1	

Hole No.	Sample#	% Sul	From	To (m)	Width	Au g/t	Ag g/t	Cu %
OPW-07-003	37201		25.0	26.0	1.0	0.11	0.6	
OPW-07-003	37202		26.0	27.0	1.0	0.11	0.8	
OPW-07-003	37216		323.0	324.0	1.0	0.10	0.1	
OPW-07-003	37217		324.0	325.0	1.0	0.83	3.6	
OPW-07-003	37236		420.0	420.4	0.4	0.11	0.4	
OPW-07-003	37240		423.0	424.0	1.0	0.33	2.4	
OPW-07-003	37243		424.0	425.0	1.0	0.20	1.1	
OPW-07-003	37244		425.0	425.3	0.3	0.94	5.3	
OPW-07-003	37245	1	427.0	428.0	1.0	0.79	5.4	
OPW-07-003	37250	1	432.0	433.0	1.0	0.10	0.8	
OPW-07-003	37253	2	463.0	464.0	1.0	0.10	2.1	
OPW-07-003	37259	2	469.0	470.0	1.0	0.14	1129.3	
OPW-07-003	37260	2	470.0	471.0	1.0	0.18	1.3	
OPW-07-003	37264	5	471.6	472.0	0.4	0.11	0.6	
OPW-07-003	37265	4	472.0	473.0	1.0	0.11	0.6	
OPW-07-003	37293	1	520.5	521.0	0.5	0.23	0.1	
OPW-07-003	37294	1	521.0	522.0	1.0	0.12	0.1	
OPW-07-004	35510	2	83.0	84.0	1.0	0.16	0.1	
OPW-07-004	35512	4	85.0	86.0	1.0	0.11	0.1	
OPW-07-004	35513	4	86.0	87.0	1.0	0.11	0.2	
OPW-07-004	35812	2	347.0	348.0	1.0	0.10	0.1	
OPW-07-004	35813	2	348.0	348.7	1.0	0.16	0.4	
OPW-07-004	35862	4	389.0	390.0	1.0	0.15	1.1	
OPW-07-004	35864	4	391.0	392.0	1.0	0.21	0.1	
OPW-07-004	35888	3	411.0	412.0	1.0	0.45	0.1	
OPW-07-004	35896	3	417.0	418.0	1.0	0.34	0.1	
OPW-07-004	35900	3	421.0	422.0	1.0	0.30	0.1	
OPW-07-004	35901	3	422.0	423.0	1.0	0.15	0.1	
OPW-07-004	35902	3	423.0	424.0	1.0	0.20	0.2	
OPW-07-004	35903	3	424.0	425.0	1.0	0.18	0.2	
OPW-07-004	35904	3	425.0	426.0	1.0	0.32	0.1	
OPW-07-004	35906	3	426.0	427.0	1.0	0.22	0.1	
OPW-07-004	35916	2	444.7	445.0	0.3	0.25	0.2	
OPW-07-004	35930	2	457.0	458.0	1.0	0.11	0.1	
OPW-07-004	35941	1	466.0	467.0	1.0	0.15	0.1	
OPW-07-004	35967	1	486.0	487.0	1.0	0.10	0.2	
OPW-07-004	35968	1	487.0	488.0	1.0	0.10	0.1	
OPW-07-004	36037	1	542.0	543.0	1.0	0.14	0.2	
OPW-07-005	36181	2	165.0	166.0	1.0	0.21	1.5	
OPW-07-006	36500	5	143.0	144.0	1.0	0.12	0.1	
OPW-07-006	36501	5	144.0	145.0	1.0	0.10	0.1	
OPW-07-006	36502	5	145.0	146.0	1.0	0.11	0.1	
OPW-07-006	36504	4	147.0	148.0	1.0	0.11	0.4	
OPW-07-006	36505	4	148.0	149.0	1.0	0.54	1.1	

Hole No.	Sample#	% Sul	From	To (m)	Width	Au g/t	Ag g/t	Cu %
OPW-07-006	36529	3	168.0	169.0	1.0	0.17	0.3	
OPW-07-006	36530	3	169.0	170.0	1.0	0.19	0.4	
OPW-07-006	36537	3	174.0	175.0	1.0	0.18	1.3	
OPW-07-006	36540	3	177.0	178.0	1.0	0.16	1.3	
OPW-07-006	36541	3	178.0	179.0	1.0	0.62	4.0	
OPW-07-006	36543	2	180.0	181.0	1.0	0.18	0.6	
OPW-07-006	36545	2	182.0	183.0	1.0	0.10	0.1	
OPW-07-006	36547	2	183.0	184.0	1.0	0.12	0.4	
OPW-07-006	36553	3	384.0	385.0	1.0	0.11	0.2	0.001
OPW-07-006	36554	3	385.0	386.0	1.0	0.26	0.1	0.001
OPW-07-006	36584	1	409.0	410.0	1.0	0.14	0.1	
OPW-07-006	36599	2	421.0	422.0	1.0	0.18	0.2	
OPW-07-006	36601	2	423.0	424.0	1.0	0.22	0.1	
OPW-07-006	36603	2	425.0	426.0	1.0	0.14	0.2	
OPW-07-006	36610	3	431.0	432.0	1.0	0.28	2.0	
OPW-07-006	36611	3	432.0	432.4	0.4	0.24	1.5	
OPW-07-007	36247	2	103.7	104.0	0.3	0.10	0.2	
OPW-07-007	36252	1	108.0	109.0	1.0	0.10	0.1	
OPW-07-007	36328	5	172.0	173.0	1.0	0.18	6.9	
OPW-07-007	36329	5	173.0	174.0	1.0	2.38	8.5	
OPW-07-007	36330	1	174.0	175.0	1.0	3.10	2.1	
	composite		173.0	175.0	2.0	2.74	5.3	
OPW-07-007	36333	1	177.0	178.0	1.0	0.24	1.1	
OPW-07-007	36358	1	198.0	199.0	1.0	0.14	0.3	
OPW-07-008	OPW-07-08		NSV					
OPW-07-009	36485	1	37.0	38.0	1.0	0.16	0.3	
OPW-07-009	36486	1	38.0	39.0	1.0	0.16	0.4	
OPW-07-009	36491	1	43.0	43.5	0.5	0.46	0.4	
OPW-07-009	36493	1	44.0	45.0	1.0	0.21	0.3	
OPW-07-010	44158	2	169.0	170.0	1.0	0.16	0.4	
OPW-07-010	44159	2	170.0	171.0	1.0	0.73	1.4	
OPW-07-010	44160	2	171.0	172.0	1.0	0.12	0.3	
OPW-07-010	44162		173.0	174.0	1.0	0.16	0.4	
OPW-07-010	44163	1	174.0	175.0	1.0	0.15	0.1	
OPW-07-010	44168	1	177.0	178.0	1.0	0.33	0.2	
OPW-07-010	44169	1	178.0	179.0	1.0	0.18	0.4	
OPW-07-010	44170	1	179.0	180.0	1.0	0.62	1.1	
OPW-07-010	44171	1	180.0	181.0	1.0	0.29	0.4	
OPW-07-010	44172	1	181.0	182.0	1.0	0.11	0.2	
OPW-07-010	44174	1	183.0	184.0	1.0	0.33	0.5	
OPW-07-010	44177		184.5	185.0	0.5	0.28	0.4	
OPW-07-010	44179		186.0	187.0	1.0	0.12	0.2	
OPW-07-010	44180		187.0	188.0	1.0	0.28	1.2	

Hole No.	Sample#	% Sul	From	To (m)	Width	Au g/t	Ag g/t	Cu %
OPW-07-010	44183		190.0	190.7	0.7	0.13	0.8	
OPW-07-011	NSV							
OPW-07-012	44049	4	203.0	204.0	1.0	0.13	0.4	0.003
OPW-07-012	44052	3	205.0	206.0	1.0	0.15	0.3	0.003
OPW-07-012	44102	1	247.0	248.0	1.0	0.13	1.0	
OPW-07-013	36629	1	16.2	17.0	0.8	0.14	0.4	0.006
OPW-07-013	36631	1	18.0	19.0	1.0	0.13	0.1	0.007
OPW-07-013	36637	1	113.5	114.0	0.5	0.45	1.0	0.006
OPW-07-013	36638	1	114.0	115.0	1.0	0.38	0.6	0.007
OPW-07-013	36639	1	115.0	116.0	1.0	0.31	0.5	0.007
OPW-07-013	36641	1	117.0	118.0	1.0	0.29	0.7	0.007
OPW-07-013	36642	1	118.0	119.0	1.0	0.15	0.5	0.008
OPW-07-013	36649	1	151.0	152.0	1.0	0.47	0.3	0.006
OPW-07-013	36650	1	152.0	153.0	1.0	0.28	0.6	0.009
OPW-07-013	36658	1	158.0	159.0	1.0	0.11	0.5	0.004
OPW-07-013	36662	1	162.0	163.0	1.0	0.11	0.2	0.006
OPW-07-013	36663	1	163.0	164.0	1.0	0.13	0.4	0.008
OPW-07-013	36670	1	169.0	170.0	1.0	0.10	0.7	0.005
OPW-07-013	36671	1	170.0	171.0	1.0	0.14	0.7	0.006
OPW-07-013	36678	1	192.0	193.0	1.0	0.22	0.7	0.004
OPW-07-013	36691	2	210.0	211.0	1.0	0.20	0.4	0.006
OPW-07-013	36692	2	211.0	212.0	1.0	0.19	0.3	0.003
OPW-07-014	36807	2	22.0	23.0	1.0	0.12	0.7	
OPW-07-014	36808	2	23.0	24.0	1.0	0.29	1.8	
OPW-07-014	36809	2	24.0	24.4	0.4	0.11	0.7	
OPW-07-014	36810	1	24.4	25.0	0.6	0.21	0.7	
OPW-07-014	36811	1	25.0	26.0	1.0	1.78	6.6	
OPW-07-014	36826	1	37.3	38.0	0.7	0.54	1.4	
OPW-07-014	36828	2	42.0	43.0	1.0	0.23	1.1	
OPW-07-014	36841	3	76.0	77.0	1.0	0.11	0.4	
OPW-07-014	36846	1	116.0	117.0	1.0	0.37	1.7	
OPW-07-014	36847	1	117.0	118.0	1.0	0.29	1.6	
OPW-07-014	36848	1	118.0	119.0	1.0	0.10	0.4	
OPW-07-014	36850	1	120.0	121.0	1.0	0.54	1.8	
OPW-07-014	36851	1	121.0	122.0	1.0	0.14	0.5	
OPW-07-014	36852	1	122.0	123.0	1.0	0.23	0.2	
OPW-07-014	36858	1	131.0	132.0	1.0	0.15	0.4	
OPW-07-014	36867	2	182.0	183.0	1.0	2.32	1.3	0.060
OPW-07-014	36868	1	183.0	183.9	0.9	0.17	0.7	0.097
OPW-07-014	36876	1	190.0	191.0	1.0	0.11	0.6	0.045
OPW-07-014	36878	1	192.0	193.0	1.0	0.10	7.9	0.315
OPW-07-014	36894	1	206.0	207.0	1.0	0.17	1.5	0.167

Hole No.	Sample#	% Sul	From	To (m)	Width	Au g/t	Ag g/t	Cu %
OPW-07-015	36706	3	101.0	101.6	0.6	0.14	0.1	
OPW-07-016	36731	2	61.0	62.0	1.0	0.90	0.5	
OPW-07-016	36732	2	62.0	63.0	1.0	0.10	0.3	
OPW-07-016	36733	2	63.0	64.0	1.0	0.22	0.3	
OPW-07-016	36734	2	64.0	65.0	1.0	0.46	0.1	
OPW-07-016	36735	2	65.0	66.0	1.0	0.13	0.4	
OPW-07-016	36736	2	66.0	67.0	1.0	0.46	0.5	
OPW-07-016	Composite		61.0	67.0	6.0	0.38	0.4	
OPW-07-016	36741	2	69.0	70.0	1.0	0.17	0.5	
OPW-07-016	36744	2	114.0	115.0	1.0	0.15	0.3	
OPW-07-016	36746	2	116.0	117.0	1.0	0.11	0.5	
OPW-07-016	36765	2	149.0	150.0	1.0	0.10	0.4	
OPW-07-016	36766	2	150.0	151.0	1.0	0.79	0.4	
OPW-07-016	36767	2	151.0	152.0	1.0	0.19	0.3	
OPW-07-016	36769	2	153.0	154.0	1.0	0.12	0.1	
OPW-07-016	36771	2	190.0	191.0	1.0	0.19	0.3	
OPW-07-016	36775	1	203.0	204.0	1.0	0.14	0.1	
OPW-07-016	36776	3	204.0	204.4	0.4	0.10	0.6	
OPW-07-017	44264	2	16.0	17.0	1.0	0.11	0.3	
OPW-07-017	44283	1	56.0	57.0	1.0	0.13	0.3	0.064
OPW-07-017	44285	1	58.0	59.0	1.0	0.38	0.4	0.047
OPW-07-017	44292	1	63.0	64.0	1.0	0.71	1.9	0.041
OPW-07-017	44296	1	67.0	68.0	1.0	0.38	1.8	0.003
OPW-07-017	44309	1	79.0	80.0	1.0	3.75	22.8	0.007
OPW-07-017	44355	3	116.0	117.0	1.0	0.41	1.1	0.105
OPW-07-017	44356	3	117.0	118.0	1.0	0.12	0.8	0.075
OPW-07-017	44357	3	118.0	119.0	1.0	0.13	0.6	0.058
OPW-07-017	44358	3	119.0	120.0	1.0	0.11	0.8	0.087
OPW-07-017	44367	2	127.0	128.0	1.0	0.11	0.5	0.112
OPW-07-017	44372	2	130.0	131.0	1.0	0.10	0.7	0.145
OPW-07-017	44373	2	131.0	132.0	1.0	0.10	0.6	0.128
OPW-07-017	44395	3	149.0	150.0	1.0	0.21	1.0	0.083
OPW-07-017	44400	1	154.0	155.0	1.0	0.11	0.4	0.093
OPW-07-017	44413	1	164.0	165.0	1.0	0.10	2.4	0.042
OPW-07-017	44414	3	165.0	166.0	1.0	0.32	4.2	0.023
OPW-07-017	44442	1	189.0	190.0	1.0	0.35	1.2	
OPW-07-017	44443	2	190.0	191.2	1.2	1.22	2.8	
OPW-07-017	44472	3	331.0	332.0	1.0	0.13	0.2	
OPW-07-017	44487	5	343.0	344.0	1.0	1.12	0.4	
Note: There are 33 samples in OPW-07-017 with > 0.1 % Cu to 0.25% Cu								
OPW-07-018	44554	3	73.3	73.6	0.3	0.15	0.4	
OPW-07-018	44598	2	167.0	168.0	1.0	0.20	0.7	
OPW-07-018	44616	2	192.0	193.0	1.0	0.18	1.6	
OPW-07-018	44617	2	193.0	194.0	1.0	0.34	2.3	

Hole No.	Sample#	% Sul	From	To (m)	Width	Au g/t	Ag g/t	Cu %
OPW-07-018	44627	1	202.0	203.0	1.0	0.12	1.0	
OPW-07-018	37365		210.0	211.0	1.0	1.15		
OPW-07-018	37366		211.0	212.0	1.0	0.10		
OPW-07-018	44646	2	290.0	291.0	1.0	0.31	0.3	
OPW-07-018	44650	2	292.0	293.0	1.0	0.18	0.6	
OPW-07-018	44651	2	293.0	294.0	1.0	0.23	0.5	
OPW-07-018	44653	2	295.0	296.1	1.1	0.14	0.7	
OPW-07-019	36931	1	423.0	424.0	1.0	0.34	0.1	
OPW-07-019	36940	1	431.0	432.0	1.0	0.13	0.1	
OPW-07-019	36942	1	433.0	434.0	1.0	0.13	0.1	
OPW-07-019	36943	1	434.0	435.0	1.0	0.17	0.1	
OPW-07-019	36947	1	436.0	437.0	1.0	0.96	0.1	
OPW-07-019	36948	1	437.0	438.0	1.0	0.34	0.1	
OPW-07-019	36949	1	438.0	439.0	1.0	0.28	0.1	
OPW-07-019	36950	1	439.0	440.0	1.0	0.71	0.3	
OPW-07-019	36951	15	440.0	441.0	1.0	2.21	0.7	
OPW-07-019	36952	8	441.0	442.0	1.0	0.89	0.3	
OPW-07-019	36953	5	442.0	443.0	1.0	0.26	0.2	
OPW-07-019	36954	15	443.0	444.0	1.0	1.24	0.4	
OPW-07-019	36956	15	444.0	445.0	1.0	0.24	0.6	
OPW-07-019	36957	5	445.0	446.0	1.0	0.10	0.2	
OPW-07-019	36958	5	446.0	447.0	1.0	0.39	0.2	
OPW-07-019	36959	5	447.0	448.0	1.0	1.41	0.5	
OPW-07-019	36960	5	448.0	449.0	1.0	1.11	0.3	
OPW-07-019	36961	5	449.0	450.0	1.0	0.77	0.3	
OPW-07-019	Composite		436.0	450.0	14.0	0.78	0.3	
OPW-07-019	36968	5	454.0	455.0	1.0	0.12	0.7	
OPW-07-019	36969	5	455.0	455.5	0.5	0.32	1.2	
OPW-07-019	36978	3	461.0	462.0	1.1	0.18	0.3	
OPW-07-019	36979	3	462.0	463.0	1.0	0.17	0.1	
OPW-07-019	36980	3	463.0	464.0	1.0	0.24	0.3	
OPW-07-019	36981	3	464.0	464.6	0.6	0.22	0.2	
OPW-07-019	36986	2	466.0	467.0	1.0	0.18	0.3	
OPW-07-019	36997	3	476.0	477.0	1.0	0.11	0.2	
OPW-07-019	36998	3	477.0	478.0	1.0	0.18	0.2	
OPW-07-019	36999	3	478.0	479.0	1.0	0.14	0.1	
OPW-07-019	37000	1	479.0	480.0	1.0	0.48	0.2	
OPW-07-019	37001	1	480.0	481.0	1.0	0.10	0.1	
OPW-07-019	37022	2	498.0	499.0	1.0	0.19	0.3	
OPW-07-019	37031	2	505.0	506.0	1.0	0.10	0.1	
OPW-07-019	37038	2	511.0	512.0	1.0	0.33	0.2	
OPW-07-019	37039	2	512.0	513.0	1.0	0.23	0.2	
OPW-07-019	37040	2	513.0	514.0	1.0	0.30	0.2	
OPW-07-019	37041	2	514.0	515.0	1.0	0.71	0.2	
OPW-07-019	37042	2	515.0	516.0	1.0	0.26	0.1	
OPW-07-019	37043	2	516.0	517.0	1.0	0.27	0.1	

Hole No.	Sample#	% Sul	From	To (m)	Width	Au g/t	Ag g/t	Cu %
OPW-07-019	37046	2	517.0	518.0	1.0	0.93	0.2	
OPW-07-019	37047	2	518.0	519.0	1.0	0.35	0.1	
OPW-07-019	37048	2	519.0	520.0	1.0	0.22	0.1	
OPW-07-019	37049	2	520.0	521.0	1.0	0.22	0.1	
OPW-07-019	37050	2	521.0	522.0	1.0	1.10	0.3	
OPW-07-019	37051	2	522.0	523.0	1.0	2.13	0.2	
OPW-07-019	Composite		511.0	523.0	12.0	0.59	0.2	
OPW-07-019	37079	2	587.0	588.0	1.0	0.12	0.7	
OPW-07-020	37095		5.7	6.5	0.8	0.11	0.4	
OPW-07-020	37096		6.5	7.5	1.0	0.20	1.0	
OPW-07-020	37098		8.0	8.7	0.7	0.16	1.5	
OPW-07-020	37101		10.7	11.7	1.0	0.12	2.3	
OPW-07-020	37118		34.4	35.0	0.6	0.11	1.9	0.264
OPW-07-020	37119		35.0	36.0	1.0	0.10	1.9	0.270
OPW-07-020	37120		36.0	37.0	1.0	0.45	5.3	0.534
OPW-07-020	37121		37.0	38.0	1.0	0.15	4.4	0.469
OPW-07-020	37122		38.0	39.2	1.2	0.23	1.6	0.141
OPW-07-020	Composite		34.4	39.2	4.8	0.22	3.0	0.333
OPW-07-020	37124		41.0	42.0	1.1	0.12	0.6	0.061
OPW-07-020	37126	8	110.4	111.0	0.6	0.10	1.1	
OPW-07-021	44678		190.0	191.0	1.0	0.12	0.8	
OPW-07-021	44681		191.0	192.0	1.0	0.20	0.5	
OPW-07-021	44682		192.0	193.0	1.0	0.11	1.1	
OPW-07-021	44697	1	525.0	526.0	1.0	0.33	0.2	
OPW-07-021	44698	1	526.0	527.0	1.0	0.10	0.5	
OPW-07-021	44701		527.0	528.0	1.0	0.20	1.1	
OPW-07-021	44714	2	574.0	575.0	1.0	0.27	1.8	0.260
OPW-07-021	44751		602.9	603.7	0.8	0.11	1.4	
OPW-07-021	44752		603.7	604.7	1.0	0.21	1.9	
OPW-07-021	44756	2	607.1	608.0	0.9	0.23	1.9	
OPW-07-022	44771		12.9	13.6	0.7	0.21	0.7	
OPW-07-022	44776		24.0	25.0	1.0	0.43	0.9	
OPW-07-022	44777		25.0	26.0	1.0	0.55	1.1	
OPW-07-022	Composite		24.0	26.0	2.0	0.49	1.0	
OPW-07-022	44828	2	203.0	204.0	1.0	0.11	0.1	
OPW-07-022	44834		208.8	210.0	1.2	0.13	0.1	
OPW-07-022	44836	1	229.3	230.3	0.9	0.30	0.7	
OPW-07-022	44894	30	517.0	518.0	1.0	0.10	15.4	

Conclusions

The drilling did not penetrate any economic mineralization but a few drill holes returned significant assays and the strike of the mineralization should be tested

with more drilling. The drilling confirmed that the Titan IP responses are caused by sulphide mineralization and that extensive zones of mineralization and alteration exist on the property. Three Titan 24 anomalies that were laid out for drilling in the first round were not drilled and should be tested. Other areas of the property have been surveyed by IP – Freewest Resources in 1995 and Opawica Explorations Inc./Northgate Minerals in 2007 (JVX Spectral IP) – with several untested IP anomalies remaining that should be investigated. Although the 2007 drilling was carried out to discover new and large deposits, the Camking Zone may warrant infill drilling along the higher grade section above 50 metres, and possibly to 100 metres, to determine if it would make ore (open pit) if processed at the Northgate Minerals Young Davidson proposed gold mill.

Recommendations

Exploration

Diamond drilling and soil sampling should be completed in a second phase program as outlined below.

Three drill holes targeting Titan 24 anomalies:

- 1) DDH 1 at 590E/810S, dip -50, azimuth 330, length 200 metres drilled to test Titan anomaly 6E-E.
- 2) DDH 2 at 410E/765S, dip -55, azimuth 330, length 400 metres drilled to test Titan anomaly 4E-G.
- 3) DDH 3 at 150E/470S, dip -70, azimuth 330, length 650 metres drilled to test Titan anomaly 2E-D.

Two drill holes targeting IP anomalies and extrapolated strike of gold intersections:

- 1) DDH 4 at 700E/1425S, dip -50, azimuth 330, length 300 metres drilled to test JVX IP anomaly, 100 metres east of intersection of 2.46 g/t Au (2.3 m) in drill hole OPW-07-001.
- 2) DDH 5 at 025E/1550S, dip -50, azimuth 330, length 300 metres drilled to test Titan anomaly 0-B, and 75 metres west of intersection of 2.74 g/t Au (2 m) in drill hole OPW-07-007, and 25 metres east of OPW-07-020 that was dyked out by diabase at IP anomaly and intersected 0.22 g/t Au and 0.333% Cu (4.8 m) above diabase.

Soil Sampling(MMI) in 4 areas:

- 1) From line 200E to 100W between 300S and 400N at 100 metre lines and 25 metre stations – 100 samples. To cover east extension of Camking fault zone, ultramafic volcanics, felsic intrusion, and sediments including several IP anomalies.
- 2) From 700E to 1200E between 1100S and 1600S at 100 metre lines and 25 metre stations – 120 samples. To cover several JVX IP anomalies in sediments.

- 3) From 700W to 1600W between BL0 and 1000S at 100 metre lines and 25 metre stations – 250 samples.
- 4) Along the North edge of the property to cover ultramafic volcanics and ultramafic to mafic intrusions at 100 metre lines and 25 metre stations – 150 samples.

Infill Drilling

Infill diamond drilling of the Camking Zone should be completed from 475W to 675W at 25 metre spacings and cutting the zone at 25 metre depth:

Nine drill holes, dip -50, azimuth 150, length 60 metres per drill hole for a total of 540 metres.

References

- Berger, B.R., Prefontaine, S. and McIlraith, S.J. 2006. Digital GIS Compilation: Bedrock Geology of Powell, Bannockburn and Montrose Townships; Ontario Geological Survey; Miscellaneous Release--Data 207. ISBN 1-4249-2567-3
- Evans, L., 2007. Technical Report of the Lower Boundary Zone, Lucky Zone, and Lower YD Zone Mineral Resource Estimates, Young-Davidson Property, Matachewan, Ontario; Prepared for Northgate Minerals Corporation; NI 43-101 Report; Scott Wilson Roscoe Postle Associates Inc.
- Lovell, H.L., 1967. Geology of the Matachewan Area; Ontario Department of Mines, Geological Report 51.

Ministry of Northern Development and Mines Assessment Files:

KL-0325

KL-0849

KL-1425

KL-1490

41P15NE0026

41P15NE2005

41P15NE2009

41P15NE2010

41P15NE2011

41P15NE8248

41P15NE8255

41P15NE8259

41P15NE8263

41P15NE8271

41P15NE8277

Certificate of Qualifications

I, Terry Arnold Link of the Town of Kirkland Lake, Province of Ontario, do hereby certify:

- 1) That I am an independent prospector and exploration contractor and reside at 13 Government Road West, Apartment # 9, P.O. Box 561, Kirkland Lake, Ontario, P2N 3J5.
- 2) That I completed—with a 4.0 GPA—the first year of the Mining Engineering Technology course at the Haileybury School of Mines, Haileybury, Ontario. (1993)
- 3) That I have worked in the field of mineral exploration as an independent prospector and exploration contractor over the past 14 years and prior to 1993 prospected part time over a period of 15 years.
- 4) That I wrote the report.

Dated at Kirkland Lake, Ontario on September 9, 2008

Terry A. Link

Matachewan Diamond Drilling Report

Appendix A

Core Logs

OPW-07-001	15 pages
OPW-07-002	6 pages
OPW-07-003	4 pages
OPW-07-004	15 pages
OPW-07-005	3 pages
OPW-07-006	3 pages
OPW-07-007	4 pages
OPW-07-008	3 pages
OPW-07-009	1 pages
OPW-07-010	2 pages
OPW-07-011	2 pages
OPW-07-012	3 pages
OPW-07-013	3 pages
OPW-07-014	3 pages
OPW-07-015	2 pages
OPW-07-016	3 pages
OPW-07-017	6 pages
OPW-07-018	4 pages
OPW-07-019	6 pages
OPW-07-020	3 pages
OPW-07-021	4 pages
OPW-07-022	6 pages

Opawica Explorations Inc.

Matachewan
 DDH#: OPW-07-001
 Az and Dip: 330/-65
 E.O.H: 600 m

GRID LOCATION: Powell Twp., Ontario
 GRID: OPW: 6E 16+00S
 UTM, type: 0523073E, 5311704N: Nad: 83 Zone: 17
 Elev.: 357

Claim: 531615, 531614, 511487
 Drill Company: Downing: NQ Core
 Start: June 20, 2007; End: June 28, 2007
 Logged by: Fred Sharpley

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %
0.00	3.42	Casing	CAS	Note, casing left in hole.										
					34001	3	3.42	4.00	0.58	Nil	0.1			
3.42	12.35	Conglomerate	CGL		34002	5	4.00	5.00	1.00	Nil	0.4			
				Very fine grained, light to medium grey unit; rounded quartz pebbles < 4 cm, occasional sericite, rare green carbonate pebble in a greywacke matrix. Disseminated pyrite, coarse grained, 3-8%; weak carbonate alteration.	34003	8	5.00	6.00	1.00	Nil	0.1			
					34004	8	6.00	7.00	1.00	Nil	0.2			
					34005	5	7.00	8.00	1.00	0.03	0.4			
					34006	5	8.00	9.00	1.00	Nil	0.3			
					34007	8	9.00	10.00	1.00	0.06	1.3			
					34008	5	10.00	11.00	1.00	Nil	0.5			
					34009	5	11.00	12.35	1.35	0.02	1			
12.35	109.00	Siltstone	SILT		34011	3	12.35	13.00	0.65	Nil	0.8			
				Very fine grained, light to medium grey unit; bedded at 30 CA; auto-brecciated at 30 CA; weak to moderately bedded.	34012	3	13.00	14.00	1.00	Nil	0.5			
				weak sericite alteration, bleached with weak quartz-sericite alteration; 2-5% disseminated pyrite	34013	3	14.00	15.00	1.00	Nil	0.3			
					34014	3	15.00	16.00	1.00	Nil	0.1			
					34015	3	16.00	17.00	1.00	0.02	0.1			
					34016	3	17.00	18.00	1.00	0.01	0.3			
				22.0-23.0 slip parallel CA	34017	3	18.00	19.00	1.00	0.01	0.3			
					34018	3	19.00	20.00	1.00	Nil	0.1			
				26.30-27.00 white quartz vein, minor pink carbonate at 60 CA.	34021	2	20.00	21.00	1.00	0.01	0.2			
					34022	2	21.00	22.00	1.00	Nil	0.3			
					34023	2	22.00	23.00	1.00	Nil	0.2			
					34024	2	23.00	24.00	1.00	0.01	0.1			
					34025	2	24.00	25.00	1.00	Nil	0.5			
					34026	1	25.00	26.00	1.00	Nil	0.4			
					34027	1	26.00	27.00	1.00	Nil	0.1			
					34028	1	27.00	28.00	1.00	Nil	0.4			
					34029	1	28.00	29.00	1.00	Nil	0.1			
					34031	1	29.00	30.00	1.00	Nil	0.1			
					34032	1	30.00	31.00	1.00	0.01	0.1			
					34033	1	31.00	32.00	1.00	Nil	0.1			
				33.0 - 54.0 traces of pyrite	34034	1	32.00	33.00	1.00	Nil	0.1			
				51.65-51.75 mud slip at 30 CA; possible fault	34035	2	54.00	55.00	1.00	Nil	0.1			
					34036	1	55.00	56.00	1.00	0.14	0.1			
					34037	3	56.00	57.00	1.00	Nil	0.1			

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %
					34038	1	57.00	58.00	1.00	0.04	0.1			
					34039	2	58.00	59.00	1.00	0.03	0.1			
					34042	1	59.00	60.00	1.00	0.03	0.1			
					34043	1	60.00	61.00	1.00	Nil	0.1			
					34044	1	61.00	62.00	1.00	0.02	0.3			
					34045	2	62.00	63.00	1.00	Nil	0.7			
				62.6 - 100.00 Siltstone Breccia: 50% angular fragments of pale yellowish, sericitic alteration in a medium grey matrix.	34046	8	63.00	64.00	1.00	Nil	0.7			
				3-7% disseminated pyrite; 1-2 mm grain size	34047	1	64.00	65.00	1.00	Nil	0.4			
					34048	1	65.00	66.00	1.00	Nil	1.1			
					34049	2	66.00	67.00	1.00	Nil	2.1			
					34050	3	67.00	68.00	1.00	0.01	2.5			
					34052	2	68.00	69.00	1.00	Nil	1.5			
					34053	3	69.00	70.00	1.00	Nil	1.3			
					34054	3	70.00	71.00	1.00	Nil	0.8			
					34055	5	71.00	72.00	1.00	Nil	1.3			
					34056	8	72.00	73.00	1.00	0.02	1.3			
					34057	8	73.00	74.00	1.00	0.01	1.7			
					34058	8	74.00	75.00	1.00	0.02	2.1			
					34059	5	75.00	76.00	1.00	Nil	0.8			
					34060	3	76.00	77.00	1.00	Nil	1.2			
					34063	5	77.00	78.00	1.00	0.02	1.3			
					34064	5	78.00	79.00	1.00	0.01	0.7			
					34065	5	79.00	80.00	1.00	Nil	1.1			
					34066	8	80.00	81.00	1.00	Nil	1.3			
					34067	5	81.00	82.00	1.00	0.02	1.9			
					34068	8	82.00	83.00	1.00	0.03	1.4			
					34069	5	83.00	84.00	1.00	0.03	1.2			
					34070	5	84.00	85.00	1.00	Nil	1.1			
					34071	8	85.00	86.00	1.00	Nil	1.2			
					34073	8	86.00	87.00	1.00	Nil	0.9			
					34074	5	87.00	88.00	1.00	Nil	0.9			
					34075	3	88.00	89.00	1.00	0.01	1.8			
					34076	3	89.00	90.00	1.00	0.03	1.1			
					34077	3	90.00	91.00	1.00	0.03	1.9			
					34078	3	91.00	92.00	1.00	0.05	1.5			
					34079	3	92.00	93.00	1.00	0.02	1.4			
					34080	3	93.00	94.00	1.00	Nil	1.2			
					34083	3	94.00	95.00	1.00	Nil	1.1			
					34084	3	95.00	96.00	1.00	Nil	0.4			
					34085	3	96.00	97.00	1.00	0.01	0.2			
					34086	3	97.00	98.00	1.00	Nil	0.1			
					34087	3	98.00	99.00	1.00	0.02	0.1			

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %
					34088	2	99.00	100.00	1.00	Nil	0.2			
					34089	2	100.00	101.00	1.00	Nil	0.1			
					34090	2	101.00	102.00	1.00	Nil	0.4			
					34091	1	102.00	103.00	1.00	Nil	1.2			
					34093	1	103.00	104.00	1.00	Nil	0.5			
					34094	1	104.00	105.00	1.00	Nil	0.2			
					34095	1	105.00	106.00	1.00	Nil	0.1			
					34096	1	106.00	107.00	1.00	0.03	0.2			
					34097	1	107.00	108.00	1.00	Nil	0.3			
					34098	1	108.00	109.00	1.00	Nil	0.1			
109.00	126.00	Greywacke	GW		34099	1	109.00	110.00	1.00	0.03	0.2			
				light to medium grey, unsorted, numerous grit sized fragments; minor quartz carbonate veining.	34100	1	110.00	111.00	1.00	0.02	0.3			
					34103	1	111.00	112.00	1.00	Nil	0.6			
					34104	1	112.00	113.00	1.00	0.02	0.3			
					34105	1	113.00	114.00	1.00	0.05	0.6			
					34106	1	114.00	115.00	1.00	Nil	0.4			
					34107	1	115.00	116.00	1.00	Nil	0.7			
					34108	1	116.00	117.00	1.00	Nil	0.8			
					34109	1	117.00	118.00	1.00	Nil	0.8			
				118.00 - 122.00 strong disseminated pyrite; 3-8% coarse grained pyrite, 1-2mm	34110	3	118.00	119.00	1.00	Nil	0.8			
					34111	5	119.00	120.00	1.00	0.06	1.1			
					34113	5	120.00	121.00	1.00	0.01	1.5			
					34114	5	121.00	122.00	1.00	0.01	0.6			
					34115	5	122.00	123.00	1.00	0.01	0.1			
					34116	5	123.00	124.00	1.00	0.01	0.1			
					34117	5	124.00	125.00	1.00	0.01	0.4			
					34118	2	125.00	126.00	1.00	0.01	0.1			
126.00	157.00	Siltstone	SILT		34119	1	126.00	127.00	1.00	0.01	0.1			
				Siltstone Breccia: as above; light grey angular fragments in greywacke matrix; weak disseminated pyrite throughout	34120	1	127.00	128.00	1.00	0.01	0.1			
				Weak bedding at 30 CA	34123	1	128.00	129.00	1.00	0.01	0.1			
					34124	1	129.00	130.00	1.00	0.01	0.1			
					34125	1	130.00	131.00	1.00	0.02	3.2			
					34126	1	131.00	132.00	1.00	0.01	0.1			
					34127	1	132.00	133.00	1.00	0.01	0.1			
					34128	1	133.00	134.00	1.00	0.01	0.1			
					34129	1	134.00	135.00	1.00	0.01	0.1			
					34130	1	135.00	136.00	1.00	0.01	0.1			
					34131	1	136.00	137.00	1.00	0.01	0.1			
					34133	1	137.00	138.00	1.00	0.01	0.1			
					34134	1	138.00	139.00	1.00	0.01	0.1			
					34135	1	139.00	140.00	1.00	0.01	0.1			
					34136	1	140.00	141.00	1.00	0.01	0.1			

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %
					34137	1	141.00	142.00	1.00	0.01	0.1			
					34138	1	142.00	143.00	1.00	0.01	0.1			
					34139	1	143.00	144.00	1.00	0.43	0.1			
					34140	1	144.00	145.00	1.00	0.04	0.7			
				144.65 traces chalcopyrite	34143	1	145.00	146.00	1.00	0.07	0.1			
					34144	1	146.00	147.00	1.00	0.01	0.1			
					34145	1	147.00	148.00	1.00	0.01	0.1			
					34146	1	148.00	149.00	1.00	0.03	0.1			
					34147	1	149.00	150.00	1.00	0.2	0.1			
					34148	1	150.00	151.00	1.00	0.01	0.1			
					34149	1	151.00	152.00	1.00	0.01	0.1			
					34150	1	152.00	153.00	1.00	0.01	0.1			
					34151	1	153.00	154.00	1.00	0.01	0.1			
					34153	1	154.00	155.00	1.00	0.01	0.5			
					34154	1	155.00	156.00	1.00	0.06	0.1			
					34155	1	156.00	157.00	1.00	0.01	0.1			
157.00	170.20	SILTSTONE	SILT	As above: weakly banded at 30 CA; < 1% disseminated pyrite.	34156	1	157.00	158.00	1.00	0.01	0.1			
					34157	1	158.00	159.00	1.00	0.01	0.1			
					34158	1	159.00	160.00	1.00	0.01	0.1			
					34159	1	160.00	161.00	1.00	0.01	0.7			
					34160	1	161.00	162.00	1.00	0.01	0.8			
					34163	1	162.00	163.00	1.00	0.02	3.4			
					34164	1	163.00	164.00	1.00	0.01	0.1			
					34165	1	164.00	165.00	1.00	0.01	0.1			
					34166	1	165.00	166.00	1.00	0.04	0.1			
					34167	1	166.00	167.00	1.00	0.03	4.1			
					34168	1	167.00	168.00	1.00	0.01	0.1			
					34169	1	168.00	169.00	1.00	0.01	0.1			
					34170	1	169.00	170.00	1.00	0.04	0.1			
					34171	3	170.00	171.00	1.00	0.01	0.1			
170.20	178.60	SILTSTONE	SILT	Siltstone Breccia: as above; light grey angular fragments in medium grey matrix; 2-3% disseminated pyrite; coarse grained in marix.	34173	5	171.00	172.00	1.00	0.01	0.1			
					34174	5	172.00	173.00	1.00	0.06	0.3			
					34175	5	173.00	174.00	1.00	0.02	0.4			
					34176	5	174.00	175.00	1.00	0.01	0.1			
					34177	2	175.00	176.00	1.00	0.01	0.4			
					34178	2	176.00	177.00	1.00	0.06	0.2			
					34179	3	177.00	178.00	1.00	0.08	0.1			
					34180	4	178.00	178.60	0.60	0.09	0.3			
178.60	181.00	LAMP	LAMP	Lamprophyre Dike:	34183	3	178.60	179.00	0.40	0.03	0.2			
				dark greenish grey, fine grained, dark amphibole and	34184	4	179.00	180.00	1.00	0.04	0.2			
				pyroxene, massive; 3-4% disseminated pyrite; 70% lamp,	34185	5	180.00	181.00	1.00	0.04	0.4			
				30% Siltstone Bx.	34186	3	181.00	182.00	1.00	0.09	1.2			

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %
181.00	244.80	SILTSTONE	SILT	Siltstone Breccia: as above; light grey angular fragments in medium grey matrix; 3-5% disseminated pyrite; coarse pyrite.	34187	3	182.00	183.00	1.00	0.1	1.3			
					34188	3	183.00	184.00	1.00	0.05	0.4			
					34189	3	184.00	185.00	1.00	0.01	0.4			
					34190	3	185.00	186.00	1.00	0.08	0.7			
					34191	4	186.00	187.00	1.00	0.04	0.7			
					34193	5	187.00	188.00	1.00	0.03	0.5			
					34194	5	188.00	189.00	1.00	0.01	1			
					34195	5	189.00	190.00	1.00	0.01	0.9			
					34196	5	190.00	191.00	1.00	0.03	0.7			
					34197	5	191.00	192.00	1.00	0.001	0.1			
					34198	3	192.00	193.00	1.00	0.06	0.1			
					34199	3	193.00	194.00	1.00	0.03	0.1			
					34200	3	194.00	195.00	1.00	0.01	0.1			
					34203	3	195.00	196.00	1.00	0.02	0.1			
					34204	8	196.00	197.00	1.00	0.01	2.1			
					34205	2	197.00	198.00	1.00	0.01	0.1			
					34206	8	198.00	199.00	1.00	0.04	0.1			
					34207	3	199.00	200.00	1.00	0.01	0.1			
					34208	4	200.00	201.00	1.00	0.03	0.4			
					34209	4	201.00	202.00	1.00	0.01	0.4			
					34210	4	202.00	203.00	1.00	0.02	0.1			
					34211	4	203.00	204.00	1.00	0.01	0.5			
					34213	3	204.00	205.00	1.00	0.01	0.3			
					34214	4	205.00	206.00	1.00	0.04	0.7			
					34215	5	206.00	207.00	1.00	0.01	0.4			
					34216	3	207.00	208.00	1.00	0.01	0.2			
					34217	5	208.00	209.00	1.00	0.01	0.3			
					34218	5	209.00	210.00	1.00	0.01	0.3			
					34219	4	210.00	211.00	1.00	0.01	0.1			
					34220	4	211.00	212.00	1.00	0.01	0.1			
					34223	4	212.00	213.00	1.00	0.01	0.1			
					34224	4	213.00	214.00	1.00	0.01	0.1			
					34225	3	214.00	215.00	1.00	0.01	0.1			
					34226	4	215.00	216.00	1.00	0.01	0.2			
					34227	4	216.00	217.00	1.00	0.01	0.2			
					34228	4	217.00	218.00	1.00	0.01	0.6			
					34229	3	218.00	219.00	1.00	0.01	0.9			
					34230	2	219.00	220.00	1.00	0.04	0.1			
					34231	3	220.00	221.00	1.00	0.01	0.2			
					34233	3	221.00	222.00	1.00	0.14	0.1			
					34234	3	222.00	223.00	1.00	0.05	0.1			
					34235	3	223.00	224.00	1.00	0.09	0.1			

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %
					34236	2	224.00	225.00	1.00	0.01	0.1			
					34237	3	225.00	226.00	1.00	0.03	0.1			
					34238	3	226.00	227.00	1.00	0.01	0.4			
					34239	3	227.00	228.00	1.00	0.01	0.9			
					34240	3	228.00	229.00	1.00	0.03	0.1			
					34243	5	229.00	230.00	1.00	0.01	0.5			
					34244	5	230.00	231.00	1.00	0.04	0.1			
					34245	5	231.00	232.00	1.00	0.01	0.1			
					34246	5	232.00	233.00	1.00	0.01	0.6			
					34247	5	233.00	234.00	1.00	0.04	0.2			
					34248	5	234.00	235.00	1.00	0.02	0.1			
					34249	5	235.00	236.00	1.00	0.01	0.1			
					34250	4	236.00	237.00	1.00	0.01	0.1			
					34251	3	237.00	238.00	1.00	0.01	0.1			
					34253	3	238.00	239.00	1.00	0.02	0.1			
					34254	3	239.00	240.00	1.00	0.01	0.1			
					34255	4	240.00	241.00	1.00	0.14	0.1			
					34256	3	241.00	242.00	1.00	0.18	0.1			
					34257	3	242.00	243.00	1.00	0.01	0.1			
					34258	3	243.00	244.00	1.00	0.07	0.1			
					34259	4	244.00	245.00	1.00	0.45	0.8			
244.80	314.60	SILTSTONE	SILT		34260	1	245.00	246.00	1.00	0.04	0.7			
				light grey, very fine grained, banded at 35 CA; minor chlorite seams; minor quartz-carbonate veining; weakly bleached; 1-3% disseminated pyrite.	34263	1	246.00	247.00	1.00	0.01	0.1			
					34264	1	247.00	248.00	1.00	0.01	0.1			
					34265	1	248.00	249.00	1.00	0.01	0.1			
					34266	1	249.00	250.00	1.00	0.01	0.1			
					34267	1	250.00	251.00	1.00	0.01	0.1			
					34268	1	251.00	252.00	1.00	0.03	1.1			
					34269	1	252.00	253.00	1.00	0.03	2			
					34270	1	253.00	254.00	1.00	0.01	1.3			
					34271	1	254.00	255.00	1.00	0.01	1.2			
					34273	1	255.00	256.00	1.00	0.02	1.1			
					34274	1	256.00	257.00	1.00	0.01	0.2			
					34275	1	257.00	258.00	1.00	0.01	0.3			
					34276	1	258.00	259.00	1.00	0.01	0.6			
					34277	1	259.00	260.00	1.00	0.01	0.1			
					34278	1	260.00	261.00	1.00	0.01	0.1			
					34279	1	261.00	262.00	1.00	0.01	0.1			
					34280	1	262.00	263.00	1.00	0.01	1.6			
					34283	1	263.00	264.00	1.00	0.01	1.2			
					34284	1	264.00	265.00	1.00	0.01	3.9			

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %
					34285	1	265.00	266.00	1.00	0.01	0.2			
					34286	1	266.00	267.00	1.00	0.01	0.1			
					34287	1	267.00	268.00	1.00	0.01	0.2			
					34288	1	268.00	269.00	1.00	0.01	0.2			
					34289	1	269.00	270.00	1.00	0.01	0.1			
					34290	1	270.00	271.00	1.00	0.03	0.2			
					34291	1	271.00	272.00	1.00	0.01	0.1			
					34293	1	272.00	273.00	1.00	0.01	0.1			
					34294	1	273.00	274.00	1.00	0.01	0.1			
					34295	1	274.00	275.00	1.00	0.03	0.1			
					34296	4	275.00	276.00	1.00	0.03	0.1			
					34297	1	276.00	277.00	1.00	0.01	0.1			
					34298	1	277.00	278.00	1.00	0.03	0.1			
					34299	1	278.00	279.00	1.00	0.01	0.1			
					34300	1	279.00	280.00	1.00	0.01	0.1			
					34303	1	280.00	281.00	1.00	0.02	0.1			
					34304	1	281.00	282.00	1.00	0.02	0.1			
					34305	1	282.00	283.00	1.00	0.01	0.1			
					34306	1	283.00	284.00	1.00	0.02	0.2			
					34307	1	284.00	285.00	1.00	0.01	0.1			
					34308	1	285.00	286.00	1.00	0.01	0.1			
					34309	1	286.00	287.00	1.00	0.01	0.2			
					34310	1	287.00	288.00	1.00	0.03	0.2			
					34311	1	288.00	289.00	1.00	0.01	0.1			
					34313	1	289.00	290.00	1.00	0.02	0.1			
					34314	1	290.00	291.00	1.00	0.01	0.3			
					34315	1	291.00	292.00	1.00	0.01	0.3			
					34316	1	292.00	293.00	1.00	0.01	0.2			
					34317	1	293.00	294.00	1.00	0.01	0.1			
					34318	1	294.00	295.00	1.00	0.01	0.2			
					34319	1	295.00	296.00	1.00	0.02	0.1			
					34320	1	296.00	297.00	1.00	0.01	0.1			
					34323	1	297.00	298.00	1.00	0.01	0.1			
					34324	1	298.00	299.00	1.00	0.01	0.1			
					34325	1	299.00	300.00	1.00	0.01	0.1			
					34326	1	300.00	301.00	1.00	0.01	0.1			
					34327	1	301.00	302.00	1.00	0.01	0.1			
					34328	1	302.00	303.00	1.00	0.01	0.1			
					34329	1	303.00	304.00	1.00	0.01	0.1			
					34330	1	304.00	305.00	1.00	0.01	0.1			
					34331	1	305.00	306.00	1.00	0.01	0.1			
					34333	1	306.00	307.00	1.00	0.01	0.1			

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %
					34334	1	307.00	308.00	1.00	0.01	0.1			
					34335	1	308.00	309.00	1.00	0.01	0.1			
					34336	1	309.00	310.00	1.00	0.01	0.1			
					34337	1	310.00	311.00	1.00	0.01	0.1			
					34338	1	311.00	312.00	1.00	0.01	0.1			
					34339	1	312.00	313.00	1.00	0.01	0.1			
					34340	1	313.00	314.00	1.00	0.07	0.1			
					34343	1	314.00	314.60	0.60	0.01	0.1			
314.60	319.90	GABBRO	GAB	Contact Zone: 70% Gabbro and 30% Siltstone: contact zones at 50 CA.	34344	1	314.60	315.00	0.40	0.01	0.1			
					34345	1	315.00	316.00	1.00	0.01	0.3			
					34346	1	316.00	317.00	1.00	0.01	0.2			
					34347	1	317.00	318.00	1.00	0.02	0.4			
					34348	1	318.00	319.00	1.00	0.01	0.1			
					34349	1	319.00	319.90	0.90	0.01	0.2			
319.90	331.50	GABBRO	GAB	dark green, medium grained, fairly massive, uniform; 60% mafic minerals, 40% plagioclase; 1-3% disseminated pyrite	34350	1	319.90	321.00	1.10	0.01	0.2			
				317.50 - 318.00 strong slips at 20 CA	34351	1	321.00	322.00	1.00	0.05	0.3			
				321.70- 322.5 strong slips at 20 CA	34353	1	322.00	323.00	1.00	0.08	0.3			
				324.7 - 325.00 strong slip at 20 CA	34354	1	323.00	324.00	1.00	0.01	0.1			
					34355	1	324.00	325.00	1.00	0.01	0.6			
					34356	15	325.00	326.00	1.00	0.09	1.6			
				325.0 - 326.0 10-30% disseminated pyrite, coarse grained, 2 mm	34357	3	326.00	327.00	1.00	0.23	0.8			
					34358	5	327.00	328.00	1.00	0.6	0.6			
					34359	4	328.00	329.00	1.00	0.21	0.4			
					34360	1	329.00	330.00	1.00	0.04	0.1			
					34363	1	330.00	331.00	1.00	0.01	0.2			
331.50	335.50	SILTSTONE	SILT	as above	34364	1	331.00	331.50	0.50	0.03	0.1			
					34365	1	331.50	332.00	0.50	0.01	0.3			
					34366	1	332.00	333.00	1.00	0.02	0.2			
					34367	1	333.00	334.00	1.00	0.01	0.2			
					34368	1	334.00	335.00	1.00	0.01	0.3			
					34369	1	335.00	335.50	0.50	0.01	0.3			
335.50	336.20	GABBRO	GAB	as above	34370	1	335.50	336.20	0.70	0.06	0.1			
					34371	1	336.20	337.00	0.80	0.01	0.2			
336.20	340.50	SILTSTONE	SILT	as above	34373	1	337.00	338.00	1.00	0.01	0.1			
					34374	1	338.00	339.00	1.00	0.01	0.1			
					34375	1	339.00	340.00	1.00	0.02	0.5			
					34376	1	340.00	340.50	0.50	0.01	0.3			
					34377	3	340.50	341.00	0.50	0.01	0.1			
340.50	356.45	QFP	QFP	QUARTZ FELDSPAR PORPHYRY:	34378	3	341.00	342.00	1.00	0.03	0.1			
				medium grey, coarse grained phenocrysts of feldspar, 5mm	34379	3	342.00	343.00	1.00	0.02	0.1			
				pink and white, and white quartz, 2mm in a medium grained	34380	3	343.00	344.00	1.00	0.08	0.2			
				grey matrix; 2-5% disseminated pyrite.	34383	5	344.00	345.00	1.00	0.01	0.1			

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %
				342.2 - 342.6 Siltstone: contacts at 50 CA	34384	5	345.00	346.00	1.00	0.01	0.4			
				342.7 - 342.8 quartz vein at 50 CA	34385	5	346.00	347.00	1.00	0.01	0.8			
				344.2-344.46 quartz albite vein at 20 CA	34386	5	347.00	348.00	1.00	0.03	0.7			
					34387	5	348.00	349.00	1.00	0.01	0.1			
					34388	5	349.00	350.00	1.00	0.04	0.1			
					34389	5	350.00	351.00	1.00	0.01	0.1			
					34390	5	351.00	352.00	1.00	0.01	0.1			
					34391	5	352.00	353.00	1.00	0.01	0.1			
				353.9 - 354.35 quartz albite vein at 20 CA	34393	5	353.00	354.00	1.00	0.03	0.1			
					34394	5	354.00	355.00	1.00	0.02	0.1			
					34395	5	355.00	356.00	1.00	0.01	0.1			
					34396	5	356.00	356.45	0.45	0.14	0.1			
356.45	374.00	SILTSTONE	SILT	as above: contact at 20 CA, 2-3% pyrite	34397	3	356.45	357.00	0.55	0.09	0.1			
					34398	2	357.00	358.00	1.00	0.01	0.1			
					34399	2	358.00	359.00	1.00	0.01	0.1			
					34400	2	359.00	360.00	1.00	0.01	0.1			
					34403	2	360.00	361.00	1.00	0.01	0.2			
					34404	2	361.00	362.00	1.00	0.01	0.1			
					34405	2	362.00	363.00	1.00	0.01	0.1			
					34406	2	363.00	364.00	1.00	0.01	0.1			
					34407	2	364.00	365.00	1.00	0.02	0.1			
					34408	2	365.00	366.00	1.00	0.01	0.1			
					34409	1	366.00	367.00	1.00	0.01	0.1			
					34410	1	367.00	368.00	1.00	0.01	0.2			
					34411	1	368.00	369.00	1.00	0.02	0.1			
					34413	1	369.00	370.00	1.00	0.01	0.1			
					34414	1	370.00	371.00	1.00	0.01	0.2			
					34415	1	371.00	372.00	1.00	0.01	0.1			
					34416	1	372.00	373.00	1.00	0.02	0.1			
					34417	1	373.00	374.00	1.00	0.01	0.2			
374.00	419.00	CGL	CGL	CONGLOMERATE: dark grey, fine grained, locally banded	34418	1	374.00	375.00	1.00	0.01	0.2			
				rounded to angular cobbles of syenite, siltstone, < 4 cm;	34419	1	375.00	376.00	1.00	0.01	0.1			
				weak bedding locally at 30 CA; locally magnetic; minor	34420	1	376.00	377.00	1.00	0.01	0.1			
				quartz carbonate veining; matrix dark grey, very fine grained	34423	1	377.00	378.00	1.00	0.01	0.1			
				grained in matrix; white quartz-carbonate veining	34424	1	378.00	379.00	1.00	0.01	0.1			
					34425	1	379.00	380.00	1.00	0.01	0.1			
					34426	1	380.00	381.00	1.00	0.01	0.1			
					34427	1	381.00	382.00	1.00	0.01	0.1			
					34428	1	382.00	383.00	1.00	0.01	0.1			
					34429	1	383.00	384.00	1.00	0.01	0.1			
					34430	1	384.00	385.00	1.00	0.01	0.1			
					34431	1	385.00	386.00	1.00	0.01	0.2			

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %
					34433	1	386.00	387.00	1.00	0.03	0.1			
					34434	1	387.00	388.00	1.00	0.01	0.1			
					34435	1	388.00	389.00	1.00	0.01	0.1			
					34436	1	389.00	390.00	1.00	0.01	0.2			
					34437	1	390.00	391.00	1.00	0.01	0.1			
					34438	1	391.00	392.00	1.00	0.01	0.2			
					34439	1	392.00	393.00	1.00	0.01	0.1			
					34440	1	393.00	394.00	1.00	0.01	0.1			
					34441	1	394.00	395.00	1.00	0.01	0.1			
					34444	1	395.00	396.00	1.00	0.01	0.1			
					34445	1	396.00	397.00	1.00	0.01	0.1			
				397.00 - 419.00 dark greenish grey, fine grained, fairly massive, flecks of biotite above; possible lamprophyre.	34446	1	397.00	398.00	1.00	0.02	0.1			
					34447	1	398.00	399.00	1.00	0.01	0.1			
					34448	1	399.00	400.00	1.00	0.01	0.1			
					34449	1	400.00	401.00	1.00	0.01	0.1			
					34450	1	401.00	402.00	1.00	0.01	0.1			
					34451	1	402.00	403.00	1.00	0.01	0.1			
					34452	1	403.00	404.00	1.00	0.01	0.1			
					34454	1	404.00	405.00	1.00	0.01	0.1			
					34455	1	405.00	406.00	1.00	0.01	0.1			
					34456	1	406.00	407.00	1.00	0.01	0.1			
					34457	1	407.00	408.00	1.00	0.01	0.1			
					34458	1	408.00	409.00	1.00	0.01	0.5			
					34459	1	409.00	410.00	1.00	0.01	0.3			
					34460	1	410.00	411.00	1.00	0.01	0.2			
					34461	1	411.00	412.00	1.00	0.01	0.2			
					34464	1	412.00	413.00	1.00	0.01	0.1			
					34465	1	413.00	414.00	1.00	0.01	0.2			
				413.8 - strong slip at 30 CA	34466	1	414.00	415.00	1.00	0.01	0.5			
				417.00 - strong slip at 50 CA	34467	1	415.00	416.00	1.00	0.01	0.1			
				414.9 - 419.00 30% quartz veining at 30 CA, minor veining	34468	1	416.00	417.00	1.00	0.01	0.1			
					34469	1	417.00	418.00	1.00	0.01	0.1			
				418.6 - 419.00 quartz vein at 40 CA	34470	1	418.00	419.00	1.00	0.07	0.2			
				419.00 - strong slip at 40 CA	34471	5	419.00	420.00	1.00	0.01	0.5			
					34472	5	420.00	421.00	1.00	0.01	0.3			
419.00	497.10	Syenite	SYN	Porphyritic Syenite:	34474	5	421.00	422.00	1.00	0.04	0.3			
				pale pink color, fine grained, <1mm, massive uniform,	34475	5	422.00	423.00		0.01	0.4			
				porphyritic, white feldspar phenocrysts, 1mm; 5-10% fine	34476	5	423.00	424.00	1.00	0.01	0.1			
				pyrite; white quartz and carbonate veining at mainly	34477	5	424.00	425.00	1.00	0.01	0.1			
				40 CA; sharp contact at 40 CA; occasional fragment of dark	34478	5	425.00	426.00	1.00	0.01	0.1			
				green greenstone; strongly fractured locally.	34479	5	426.00	427.00	1.00	0.01	0.1			
					34480	5	427.00	428.00	1.00	0.01	0.4			

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %
				428.40 - 3 cm quartz vein at 40 CA	34481	5	428.00	429.00	1.00	0.01	0.2			
					34484	5	429.00	430.00	1.00	0.01	0.6			
					34485	5	430.00	431.00	1.00	0.01	0.4			
				432.8 - 3 cm quartz vein at 60 CA	34486	5	431.00	432.00	1.00	0.01	0.1			
				432.35 - 1 cm quartz vein at 40 CA	34487	5	432.00	433.00	1.00	0.01	0.3			
				432.90 - 2 cm quartz vein at parallel	34488	5	433.00	434.00	1.00	0.01	0.1			
				433.6 - 4 cm quartz vein at 50 CA	34489	5	434.00	435.00	1.00	0.01	0.2			
					34490	5	435.00	436.00	1.00	0.01	0.2			
					34491	5	436.00	437.00	1.00	0.01	0.1			
					34492	5	437.00	438.00	1.00	0.01	0.1			
					34494	5	438.00	439.00	1.00	0.01	0.1			
				438.66 - 4 cm quartz vein at 40 CA	34495	5	439.00	440.00	1.00	0.01	0.1			
					34496	5	440.00	441.00	1.00	0.01	0.4			
					34497	5	441.00	442.00	1.00	0.01	0.1			
					34498	5	442.00	443.00	1.00	0.01	0.1			
					34499	5	443.00	444.00	1.00	0.01	0.1			
					34500	5	444.00	445.00	1.00	0.01	0.1			
					34501	5	445.00	446.00	1.00	0.01	0.1			
					34504	5	446.00	447.00	1.00	0.01	0.4			
					34505	5	447.00	448.00	1.00	0.01	0.1			
					34506	5	448.00	449.00	1.00	0.01	0.2			
					34507	5	449.00	450.00	1.00	0.01	0.1			
					34508	5	450.00	451.00	1.00	0.01	0.1			
					34509	5	451.00	452.00	1.00	0.01	0.3			
					34510	5	452.00	453.00	1.00	0.01	0.1			
					34511	5	453.00	454.00	1.00	0.01	0.2			
					34513	5	454.00	455.00	1.00	0.01	0.2			
					34514	5	455.00	456.00	1.00	Nil	0.3			
					34515	5	456.00	457.00	1.00	Nil	0.3			
					34516	5	457.00	458.00	1.00	Nil	0.1			
				458.5 - 458.7 quartz veining at 40 CA	34517	5	458.00	459.00	1.00	Nil	0.1			
					34518	5	459.00	460.00	1.00	Nil	0.1			
				459.9 - 4 cm quartz vein at 20 CA	34519	5	460.00	461.00	1.00	0.03	0.1			
					34520	5	461.00	462.00	1.00	0.02	0.1			
					34523	5	462.00	463.00	1.00	Nil	0.1			
					34524	5	463.00	464.00	1.00	Nil	0.1			
					34525	5	464.00	465.00	1.00	Nil	0.1			
					34526	5	465.00	466.00	1.00	0.01	0.1			
					34527	5	466.00	467.00	1.00	0.03	0.1			
					34528	5	467.00	468.00	1.00	0.03	0.1			
					34529	5	468.00	469.00	1.00	Nil	0.1			
					34530	5	469.00	470.00	1.00	Nil	0.1			

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %
					34531	5	470.00	471.00	1.00	Nil	0.1			
					34533	5	471.00	472.00	1.00	Nil	0.2			
					34534	5	472.00	473.00	1.00	0.12	0.1			
					34535	5	473.00	474.00	1.00	0.1	0.1			
				474.96 - 1 cm quartz vein at 70 CA	34536	5	474.00	475.00	1.00	0.01	0.1			
					34537	5	475.00	476.00	1.00	0.05	0.1			
				472.65 - 2 cm quartz vein at 40 CA	34538	5	476.00	477.00	1.00	0.11	0.1			
				473.8 - 2 cm quartz vein at 40 CA	34539	5	477.00	478.00	1.00	0.02	0.1			
				475.96 - 1 cm quartz vein at 70 CA	34540	5	478.00	479.00	1.00	0.02	0.1			
					34543	5	479.00	480.00	1.00	Nil	0.1			
					34544	5	480.00	481.00	1.00	Nil	0.1			
					34545	5	481.00	482.00	1.00	0.03	0.1			
					34546	5	482.00	483.00	1.00	Nil	0.1			
					34547	5	483.00	484.00	1.00	Nil	0.1			
					34548	5	484.00	485.00	1.00	Nil	0.1			
					34549	5	485.00	486.00	1.00	0.01	0.1			
					34550	5	486.00	487.00	1.00	Nil	0.1			
				486.9 - 3 cm quartz vein at 50 CA	34551	5	487.00	488.00	1.00	Nil	0.1			
					34553	5	488.00	489.00	1.00	Nil	0.1			
					34554	5	489.00	490.00	1.00	Nil	0.1			
					34555	5	490.00	491.00	1.00	Nil	0.1			
					34556	5	491.00	492.00	1.00	Nil	0.1			
					34557	5	492.00	493.00	1.00	Nil	0.1			
					34558	5	493.00	494.00	1.00	0.05	0.1			
					34559	5	494.00	495.00	1.00	Nil	0.1			
					34560	5	495.00	496.00	1.00	Nil	0.1			
				vague lower contact at 40-50 CA	34563	5	496.00	497.10	1.10	0.01	0.1	0.0007		
497.10	564.25	CGL	CGL	497.5, 501.4, 505.5, 506.4 traces of chalcopyrite in quartz carbonate veins	34564	2	497.10	498.00	0.90	0.01	0.1	0.0007		
				Conglomerate: as above: pebbles of greenstone and granite scattered quartz carbonate veining at 30-40 CA	34565	2	498.00	499.00	1.00	0.01	0.1	0.0049		
					34566	2	499.00	500.00	1.00	0.04	0.1	0.0124		
					34567	2	500.00	501.00	1.00	0.01	0.1	0.0071		
					34568	2	501.00	502.00	1.00	0.01	0.1	0.0113		
				497.1 - 519.00 dark green groundmass with biotite and hornblende <1mm	34569	2	502.00	503.00	1.00	0.01	0.2	0.0052		
					34570	2	503.00	504.00	1.00	0.01	0.3	0.0043		
					34571	2	504.00	505.00	1.00	0.01	0.1	0.0009		
					34573	2	505.00	506.00	1.00	0.01	0.1	0.0116		
					34574	2	506.00	507.00	1.00	0.01	0.2	0.0385		
					34575	2	507.00	508.00	1.00	0.01	0.1	0.0007		
					34576	2	508.00	509.00	1.00	0.53	0.1	0.0004		
					34577	2	509.00	510.00	1.00	0.01	0.1	0.0003		
					34578	2	510.00	511.00	1.00	0.01	0.1	0.0023		
					34579	2	511.00	512.00	1.00	0.01	0.1	0.0094		

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %
					34580	2	512.00	513.00	1.00	0.01	0.1	0.0085		
					34583	2	513.00	514.00	1.00	0.01	0.1	0.0026		
					34584	2	514.00	515.00	1.00	0.01	0.3	0.0027		
					34585	2	515.00	516.00	1.00	0.01	0.1	0.0041		
					34586	2	516.00	517.00	1.00	0.01	0.1	0.0032		
					34587	2	517.00	518.00	1.00	0.01	0.1	0.0173		
					34588	2	518.00	519.00	1.00	0.01	0.1	0.0056		
					34589	2	519.00	520.00	1.00	0.01	0.1	0.008		
					34590	2	520.00	521.00	1.00	0.01	0.1	0.0062		
					34592	2	521.00	522.00	1.00	0.01	0.1	0.0014		
					34593	2	522.00	523.00	1.00	0.02	0.1	0.0041		
					34594	2	523.00	524.00	1.00	0.05	0.2	0.0115		
					34595	2	524.00	525.00	1.00	0.35	0.1	0.0058		
					34596	2	525.00	526.00	1.00	0.1	0.2	0.0078		
					34597	2	526.00	527.00	1.00	0.02	0.1	0.0135		
					34598	2	527.00	528.00	1.00	0.02	0.1	0.0052		
					34599	2	528.00	529.00	1.00	0.01	0.1	0.0057		
					34602	2	529.00	530.00	1.00	0.02	0.1	0.0073		
					34603	2	530.00	531.00	1.00	0.02	0.1	0.0057		
					34604	2	531.00	532.00	1.00	0.02	0.1	0.0051		
					34605	2	532.00	533.00	1.00	0.03	0.1	0.0064		
					34606	2	533.00	534.00	1.00	0.02	0.1	0.0041		
					34607	2	534.00	535.00	1.00	0.01	0.1	0.0039		
					34608	2	535.00	536.00	1.00	0.07	0.1	0.0055		
					34609	2	536.00	537.00	1.00	0.01	0.1	0.0033		
					34610	2	537.00	538.00	1.00	0.02	0.1	0.0021		
					34612	2	538.00	539.00	1.00	0.01	0.1	0.0037		
					34613	2	539.00	540.00	1.00	0.02	0.1	0.0031		
					34614	2	540.00	541.00	1.00	0.01	0.1	0.0033		
					34615	2	541.00	542.00	1.00	0.23	0.1	0.0044		
					34616	2	542.00	543.00	1.00	0.02	0.1	0.0036		
					34617	2	543.00	544.00	1.00	0.05	0.1	0.0021		
					34618	2	544.00	545.00	1.00	0.01	0.1	0.0026		
					34621	2	545.00	546.00	1.00	0.07	0.1	0.0045		
					34622	2	546.00	547.00	1.00	0.03	0.1	0.0045		
					34623	2	547.00	548.00	1.00	0.01	0.1	0.0023		
					34624	2	548.00	549.00	1.00	0.03	0.1	0.0016		
				548.6 - trace of chalcopyrite	34625	2	549.00	550.00	1.00	0.04	0.2	0.0551		
					34626	2	550.00	551.00	1.00	0.03	0.1	0.0163		
					34627	2	551.00	552.00	1.00	0.03	0.1	0.0046		
					34628	2	552.00	553.00	1.00	0.08	0.1	0.0018		
					34629	2	553.00	554.00	1.00	0.02	0.1	0.0015		

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %
					34631	2	554.00	555.00	1.00	0.02	0.1	0.0019		
					34632	2	555.00	556.00	1.00	0.16	0.1	0.0016		
					34633	2	556.00	557.00	1.00	0.01	0.1	0.0017		
					34634	2	557.00	558.00	1.00	0.35	0.1	0.0055		
					34635	2	558.00	559.00	1.00	0.33	0.1	0.0057		
					34636	2	559.00	560.00	1.00	0.13	0.1	0.0046		
					34637	2	560.00	561.00	1.00	0.47	0.1	0.0055		
					34638	3	561.00	562.00	1.00	0.26	0.1	0.0033		
					34641	3	562.00	563.00	1.00	1.28	0.2	0.0031		
					34642	3	563.00	564.25	1.25	3.41	0.6	0.0067		
564.25	566.23	LAM	LAM	LAMPROPHYRE DIKE: contacts at 60-70 CA	34643		564.25	565.00	0.75	0.01	0.2	0.0257		
				medium green color, fine grained, massive, hornblende	34644		565.00	566.23	1.23	0.01	0.2	0.0082		
				crystals, fine-grained, <1mm in a very fine-grained matrix.	34645	3	566.23	567.00	0.77	0.01	0.1	0.0035		
				contact at 60-70 CA.	34646	3	567.00	568.00	1.00	0.01	0.2	0.0056		
566.23	571.35	CGL	CGL	CONGLOMERATE: as above	34647	3	568.00	569.00	1.00	0.03	0.1	0.0059		
					34648	3	569.00	570.00	1.00	0.01	0.1	0.0085		
					34649	3	570.00	571.35	1.35	0.05	0.1	0.0091		
571.35	572.66	LAM	LAM	LAMPROPHYRE: as above: contact at 40-50 CA	34651		571.35	572.66	1.31	0.02	0.1			
572.66	585.10	CGL	CGL	CONGLOMERATE: as above	34652	3	572.66	573.00	0.34	0.01	0.1			
					34653	3	573.00	574.00	1.00	0.02	0.1			
					34654	3	574.00	575.00	1.00	0.01	0.1			
					34655	3	575.00	576.00	1.00	0.01	0.1			
					34656	3	576.00	577.00	1.00	0.01	0.1			
					34657	2	577.00	578.00	1.00	0.01	0.1			
					34658	2	578.00	579.00	1.00	0.01	0.1			
					34661	2	579.00	580.00	1.00	0.01	0.1			
					34662	2	580.00	581.00	1.00	0.01	0.1			
					34663	2	581.00	582.00	1.00	0.01	0.1			
					34664	2	582.00	583.00	1.00	0.02	0.1			
					34665	2	583.00	584.00	1.00	0.03	0.1			
					34666	2	584.00	585.00	1.00	0.01	0.1			
585.10	588.80	LAM	LAM	LAMPROPHYRE: as above: contact at 40 CA	34667		585.00	586.00	1.00	0.06	0.1			
					34668		586.00	587.00	1.00	0.12	0.2			
					34669		587.00	588.00	1.00	0.05	0.1			
					34671	2	588.00	589.00	1.00	0.01	0.1			
588.80	591.70	CGL	CGL	CONGLOMERATE: as above: contacts at 40-CA	34672	2	589.00	590.00	1.00	0.01	0.1			
					34673	2	590.00	591.00	1.00	0.01	0.1			
					34674	2	591.00	591.70	0.70	0.01	0.1			
591.70	594.70	LAM	LAM	LAMPROPHYRE: as above: contact at 30-40 CA	34675		591.70	593.00	1.30	0.01	0.1			
					34676		593.00	594.00	1.00	0.02	0.1			
					34677	2	594.00	595.00	1.00	0.02	0.1			
594.70	600.00	CGL	CGL	CONGLOMERATE: as above: contacts at 40-CA	34678	2	595.00	596.00	1.00	0.01	0.1			

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %
				597.15 - 597.60 Lamprophyre Dike: as above: contact at	34681	2	596.00	597.00	1.00	0.02	0.2			
				70 CA	34682	2	597.00	598.00	1.00	0.01	0.1			
				599.55 - 600.00 Lamprophyre Dike: as above: contact at	34683	2	598.00	599.00	1.00	0.01	0.1			
				30 CA	34684	2	599.00	600.00	1.00	0.01	0.1			
				EOH										
				Note: core stored at Matachewan.										
Downhole Tests:														
	Depth	AZ	DIP											
	51	334.1	-63.9											
	102	336.3	-64.2											
	149	336.3	-63.9											
	201	339.7	-63.1											
	251	341.8	-63											
	302	342.5	-61.8											
	351	340.1	-59.9											
	405	344.3	-59											
	453	346.4	-57.4											
	504	344.6	-57.7											
	555	342.5	-56.5											
	600	344.1	-55.7											

Opawica Explorations Inc.

Matachewan
DDH#: OPW-07-002
Az and Dip: 330/-55
E.O.H: 201 m

GRID LOCATION: Powell Twp., Ontario
GRID: OPW: 4E 16+45S
UTM, type: 0522948E, 5311612N: Nad: 83 Zone: 17
Elev.:

Claim: 531615, MR37455
Drill Company: Downing: NQ Core
Start: July 04, 2007; End: July 06, 2007
Logged by: Fred Sharpley

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
0.00	4.64	Casing	CAS	Note, casing left in hole.	34685	5	4.64	5.00	0.36	0.04	0.8	0.023			
					34686	3	5.00	6.00	1.00	0.08	0.4	0.020			
4.64	36.00	Conglomerate	CGL		34687	3	6.00	7.00	1.00	0.19	0.3	0.009			
				Very fine grained, light to medium grey unit; rounded quartz pebbles < 4 cm, occasional sericite, rare green carbonate pebble in a greywacke matrix. Disseminated	34688	3	7.00	8.00	1.00	0.47	1	0.030			
					34689	3	8.00	9.00	1.00	0.81	1.6	0.036			
					34690	3	9.00	10.00	1.00	Nil	0.4	0.033			
				pyrite, coarse grained, 1-3%; weak carbonate alteration. weakly banded to foliated at 40-50 CA; traces of chalcopryite	34691	3	10.00	11.00	1.00	0.08	0.2	0.008			
				minor quartz carbonate veining at 40 CA	34692	2	11.00	12.00	1.00	0.03	0.2	0.008			
					34693	2	12.00	13.00	1.00	0.04	0.2	0.013			
					34695	2	13.00	14.00	1.00	0.04	0.2	0.020			
				8.00 - 9.70 weakly sheared at 30 and 60 CA; moderate disseminated pyrite, traces chalcopryite	34696	2	14.00	15.00	1.00	0.04	0.2	0.014			
					34697	2	15.00	16.00	1.00	0.03	0.2	0.010			
					34698	2	16.00	17.00	1.00	0.02	0.3	0.016			
					34699	2	17.00	18.00	1.00	0.02	0.3	0.010			
					34700	2	18.00	19.00	1.00	0.13	0.2	0.016			
					34701	2	19.00	20.00	1.00	0.05	0.5	0.019			
					34702	2	20.00	21.00	1.00	0.06	0.5	0.024			
					34705	1	21.00	22.00	1.00	0.03	0.8	0.052			
					34706	1	22.00	23.00	1.00	0.08	1.2	0.043			
					34707	1	23.00	24.00	1.00	0.03	1.1	0.017			
					34708	1	24.00	25.00	1.00	0.04	9.2	0.053			
					34709	1	25.00	26.00	1.00	Nil	0.5	0.016			
					34710	1	26.00	27.00	1.00	0.02	0.7	0.012			
					34711	1	27.00	28.00	1.00	Nil	0.4	0.018			
					34712	1	28.00	29.00	1.00	Nil	2.1	0.021			
					34713	1	29.00	30.00	1.00	0.02	0.2	0.009			
				30.00 - 34.70 numerous chlorite slips at 30 and 60 CA chloritized	34715	2	30.00	31.00	1.00	0.01	1.3	0.013			
					34716	2	31.00	32.00	1.00	0.02	0.1	0.001			
					34717	2	32.00	33.00	1.00	0.13	0.3	0.000			
					34718	2	33.00	34.00	1.00	0.01	0.1	0.000			
					34719	2	34.00	35.00	1.00	0.01	2.1	0.025			
					34720	2	35.00	36.00	1.00	0.02	2.8	0.015			
36.00	119.30	CGL	CGL	36.0 -119.3 Alteration Zone: sericite-chlorite: moderate-	34721	3	36.00	37.00	1.00	0.02	2	0.008			

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
				str. alteration; 3-5% disseminated pyrite, coarse grained,	34722	3	37.00	38.00	1.00	0.03	1.6	0.017			
				1-2mm; traces chalcopyrite; resembles felsic fragmental,	34725	3	38.00	39.00	1.00	0.01	2.1	0.011			
				fragments subrounded, quartz, green carbonate minor,	34726	3	39.00	40.00	1.00	0.04	1.7	0.010			
				sericitized felsic fragments	34727	3	40.00	41.00	1.00	0.11	1	0.015			
					34728	3	41.00	42.00	1.00	Nil	0.6	0.012			
					34729	5	42.00	43.00	1.00	0.02	0.8	0.019			
					34730	5	43.00	44.00	1.00	0.01	0.8	0.010			
					34731	5	44.00	45.00	1.00	0.02	1	0.023			
					34732	5	45.00	46.00	1.00	0.03	1.2	0.021			
					34733	5	46.00	47.00	1.00	0.03	1.8	0.010			
					34735	5	47.00	48.00	1.00	0.02	1	0.008			
					34736	5	48.00	49.00	1.00	0.08	3.2	0.021			
					34737	5	49.00	50.00	1.00	0.02	1	0.018			
					34738	5	50.00	51.00	1.00	0.02	0.7	0.004			
					34739	5	51.00	52.00	1.00	Nil	1	0.025			
					34740	3	52.00	53.00	1.00	0.01	0.5	0.007			
					34741	3	53.00	54.00	1.00	0.02	1.1	0.008			
					34742	3	54.00	55.00	1.00	0.05	1.7	0.031			
					34745	5	55.00	56.00	1.00	0.08	1.2	0.038			
					34746	5	56.00	57.00	1.00	0.1	1.1	0.009			
					34747	5	57.00	58.00	1.00	0.03	1.2	0.004			
					34748	5	58.00	59.00	1.00	0.02	0.8	0.004			
					34749	3	59.00	60.00	1.00	0.04	0.8	0.008			
					34750	3	60.00	61.00	1.00	0.02	0.4	0.005			
					34751	3	61.00	62.00	1.00	0.2	0.5	0.036			
					34752	3	62.00	63.00	1.00	0.18	0.9	0.018			
					34753	3	63.00	64.00	1.00	0.07	1.4	0.013			
					34755	3	64.00	65.00	1.00	0.04	1.5	0.006			
					34756	3	65.00	66.00	1.00	0.04	2	0.007			
					34757	3	66.00	67.00	1.00	0.09	0.8	0.005			
					34758	3	67.00	68.00	1.00	Nil	0.5	0.004			
					34759	3	68.00	69.00	1.00	0.03	0.3	0.003			
					34760	3	69.00	70.00	1.00	0.21	1.1	0.004			
					34761	3	70.00	71.00	1.00	0.04	2.4	0.004			
					34762	3	71.00	72.00	1.00	0.02	1.6	0.005			
					34765	5	72.00	73.00	1.00	0.11	1	0.007			
					34766	5	73.00	74.00	1.00	0.02	1.3	0.004			
					34767	5	74.00	75.00	1.00	0.04	1.7	0.005			
					34768	5	75.00	76.00	1.00	0.03	1.2	0.004			

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					34769	5	76.00	77.00	1.00	0.03	2.4	0.005			
					34770	5	77.00	78.00	1.00	0.01	1.8	0.004			
					34771	5	78.00	79.00	1.00	0.01	1.50	0.004			
					34772	5	79.00	80.00	1.00	0.04	2.50	0.004			
					34773	5	80.00	81.00	1.00	0.03	2.20	0.005			
					34775	5	81.00	82.00	1.00	0.04	1.60	0.005			
					34776	5	82.00	83.00	1.00	0.04	1.10	0.005			
					34777	5	83.00	84.00	1.00	0.28	0.50	0.023			
					34778	5	84.00	85.00	1.00	0.10	0.80	0.008			
					34779	5	85.00	86.00	1.00	0.04	0.70	0.005			
					34780	5	86.00	87.00	1.00	0.03	1.30	0.008			
					34781	5	87.00	88.00	1.00	0.05	1.20	0.012			
					34782	5	88.00	89.00	1.00	0.05	0.80	0.011			
					34785	5	89.00	90.00	1.00	0.36	0.40	0.007			
					34786	5	90.00	91.00	1.00	0.11	0.50	0.009			
					34787	5	91.00	92.00	1.00	0.02	0.70	0.004			
					34788	5	92.00	93.00	1.00	0.02	0.90	0.004			
					34789	5	93.00	94.00	1.00	0.02	0.90	0.004			
					34790	5	94.00	95.00	1.00	0.01	0.80	0.003			
					34791	5	95.00	96.00	1.00	0.02	0.50	0.005			
					34792	3	96.00	97.00	1.00	0.01	1.10	0.004			
					34793	3	97.00	98.00	1.00	0.02	1.00	0.006			
					34795	3	98.00	99.00	1.00	0.01	0.70	0.009			
					34796	3	99.00	100.00	1.00	0.04	1.00	0.003			
					34797	3	100.00	101.00	1.00	0.01	0.90	0.008			
					34798	3	101.00	102.00	1.00	0.01	0.50	0.018			
					34799	3	102.00	103.00	1.00	0.04	0.50	0.009			
					34800	3	103.00	104.00	1.00	0.05	0.40	0.007			
					34801	3	104.00	105.00	1.00	0.04	0.40	0.007			
					34802		105.00	106.00	1.00	0.01	0.50	0.018			
					34805	3	106.00	107.00	1.00	0.01	0.40	0.002			
					34806	3	107.00	108.00	1.00	0.01	0.40	0.002			
					34807	3	108.00	109.00	1.00	0.01	0.30	0.002			
					34808	3	109.00	110.00	1.00	0.01	0.40	0.021			
					34809	3	110.00	111.00	1.00	0.01	0.50	0.018			
					34810	3	111.00	112.00	1.00	0.01	0.80	0.009			
					34811	3	112.00	113.00	1.00	0.01	0.70	0.008			
					34812	3	113.00	114.00	1.00	0.01	0.90	0.011			
					34813	3	114.00	115.00	1.00	0.01	0.90	0.015			
					34815	3	115.00	116.00	1.00	0.01	1.00	0.013			
					34816	3	116.00	117.00	1.00	0.04	2.40	0.028			
					34817	3	117.00	118.00	1.00	0.01	1.60	0.027			

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					34818	3	118.00	119.00	1.00	0.01	1.10	0.017			
119.30	156.00	CGL	CGL	CONGLOMERATE: as above	34819	1	119.00	120.00	1.00	0.01	1.30	0.015			
					34820	1	120.00	121.00	1.00	0.01	0.90	0.007			
				119.30- 132.40 weakly chloritized conglomerate	34821	1	121.00	122.00	1.00	0.01	0.80	0.009			
					34822	1	122.00	123.00	1.00	0.01	0.10	0.001			
				123.40 - 124.40 20% quartz veining at 50 and 70 CA	34825	1	123.00	124.00	1.00	0.01	0.10	0.001			
					34826	1	124.00	125.00	1.00	0.04	0.10	0.001			
					34827	1	125.00	126.00	1.00	0.01	0.10	0.001			
					34828	1	126.00	127.00	1.00	0.01	0.10	0.001			
					34829	1	127.00	128.00	1.00	0.01	0.10	0.001			
					34830	1	128.00	129.00	1.00	0.01	0.10	0.001			
					34831	1	129.00	130.00	1.00	0.01	0.20	0.001			
					34832	1	130.00	131.00	1.00	0.01	2.30	0.021			
					34833	1	131.00	132.00	1.00	0.01	1.20	0.007			
				132.40 - 142.00 light grey, bleached, weakly altered; 1-3% disseminated pyrite, traces chalcopyrite	34835	2	132.00	133.00	1.00	0.01	1.00	0.037			
					34836	2	133.00	134.00	1.00	0.01	1.50	0.043			
					34837	2	134.00	135.00	1.00	0.03	0.40	0.076			
					34838	2	135.00	136.00	1.00	0.03	1.40	0.201			
					34839	2	136.00	137.00	1.00	0.01	0.90	0.081			
					34840	2	137.00	138.00	1.00	0.01	0.60	0.016			
					34841	2	138.00	139.00	1.00	0.01	0.40	0.045			
					34842	2	139.00	140.00	1.00	0.03	0.80	0.039			
					34843	2	140.00	141.00	1.00	0.02	1.60	0.058			
					34846	2	141.00	142.00	1.00	0.01	0.30	0.034			
				142.00 - 156.00 chloritized conglomerate	34847	1	142.00	143.00	1.00	0.04	1.00	0.015			
					34848	1	143.00	144.00	1.00	0.01	0.10	0.015			
					34849	1	144.00	145.00	1.00	0.01	0.20	0.012			
					34850	1	145.00	146.00	1.00	0.01	0.40	0.036			
					34851	1	146.00	147.00	1.00	0.04	0.30				
					34852	1	147.00	148.00	1.00	0.05	0.10				
					34853	1	148.00	149.00	1.00	0.04	0.40				
					34854	1	149.00	150.00	1.00	0.01	0.10				
					34856	1	150.00	151.00	1.00	0.02	0.10				
					34857	1	151.00	152.00	1.00	0.01	0.10				
					34858	1	152.00	153.00	1.00	0.01	0.10				
					34859	1	153.00	154.00	1.00	0.01	0.20				
					34860	1	154.00	155.00	1.00	0.01	0.80				
					34861	1	155.00	156.00	1.00	0.03	0.40				
156.00	156.40	DIO	DIO	Mafic Dike: dark grey, very fine grined, massive uniform sharp contact ar 30 CA	34862		156.00	157.00	1.00	0.01	0.10				
					34863	1	157.00	158.00	1.00	0.02	0.30				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
156.40	172.84	CGL	CGL	CONGLOMERATE: as above	34866	1	158.00	159.00	1.00	0.01	0.10				
					34867	1	159.00	160.00	1.00	0.01	0.10				
					34868	1	160.00	161.00	1.00	0.01	0.10				
					34869	1	161.00	162.00	1.00	0.01	0.20				
					34870	1	162.00	163.00	1.00	0.01	0.20				
					34871	1	163.00	164.00	1.00	0.01	0.20				
					34872	1	164.00	165.00	1.00	0.02	0.40				
					34873	1	165.00	166.00	1.00	0.01	0.10				
					34875	1	166.00	167.00	1.00	0.01	0.10				
					34876	1	167.00	168.00	1.00	0.01	0.40				
					34877	1	168.00	169.00	1.00	0.01	0.10				
					34878	1	169.00	170.00	1.00	0.01	0.30				
					34879	1	170.00	171.00	1.00	0.01	0.30				
					34880	1	171.00	172.00	1.00	0.01	0.50				
172.84	183.10	SILTSTONE	SILT	light grey, fine grained, weakly banded at 30-50 CA	34881	1	172.00	173.00	1.00	0.03	0.40				
					34882	1	173.00	174.00	1.00	0.01	0.30				
					34885	1	174.00	175.00	1.00	0.01	0.40				
					34886	1	175.00	176.00	1.00	0.01	0.10				
					34887	1	176.00	177.00	1.00	0.01	0.40				
					34888	1	177.00	178.00	1.00	0.02	0.20				
					34889	1	178.00	179.00	1.00	0.01	0.10				
					34890	1	179.00	180.00	1.00	0.01	0.20				
					34891	1	180.00	181.00	1.00	0.01	0.20				
					34892	1	181.00	182.00	1.00	0.01	0.30				
					34893	1	182.00	183.00	1.00	0.02	0.10				
183.10	201.00	CGL	CGL	as above:	34895	1	183.00	184.00	1.00	0.01	0.10				
					34896	1	184.00	185.00	1.00	0.01	0.10				
					34897	1	185.00	186.00	1.00	0.01	0.10				
					34898	1	186.00	187.00	1.00	0.01	0.10				
					34899	1	187.00	188.00	1.00	0.02	0.10				
					34900	1	188.00	189.00	1.00	0.02	0.10				
					34901	1	189.00	190.00	1.00	0.04	0.10				
					34902	1	190.00	191.00	1.00	0.03	0.30				
					34905	1	191.00	192.00	1.00	0.01	0.30				
					34906	1	192.00	193.00	1.00	0.03	0.20				
					34907	1	193.00	194.00	1.00	0.02	0.30				
					34908	1	194.00	195.00	1.00	0.03	0.20				
					34909	1	195.00	196.00	1.00	0.01	0.20				
					34910	1	196.00	197.00	1.00	0.04	0.40				
					34911	1	197.00	198.00	1.00	0.02	0.30				
					34912	1	198.00	199.00	1.00	0.01	0.40				
					34913	1	199.00	200.00	1.00	0.01	0.30				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
				EOH	34915	1	200.00	201.00	1.00	0.02	0.30				
				Core stored at Matachewan											
Downhole Tests:															
	Depth	AZ	DIP												
	54	330.5	-54.6												
	102	330.9	-53.3												
	156	332	-50.8												
	201	332	-50.8												

Opawica Explorations Inc.

Matachewan
 DDH#: OPW-07-003
 Az and Dip: 150/-60
 E.O.H: 597 m

GRID LOCATION: Powell Twp., Ontario
 GRID: OPW: 4W 0+30S
 UTM, type: 0521454E, 5312600N: Nad: 83 Zone: 17
 Elev.: 360

Claim: L372910, 3006742
 Drill Company: Downing: NQ Core
 Start: July 06, 2007; End: July 11, 2007
 Logged by: Fred Sharpley

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
0.00	4.10		OVB												
4.10	17.00	Siltstone	SILT	light grey, fine grained, weakly banded at 50 CA											
				8.60-9.30 sheared quartz carbonate vein at 40 CA; 1-3% disseminated pyrite	37180	2	8.00	8.60	0.60	0.14	0.70				
					37181		8.60	9.30	0.70	0.29	0.80				
					37182		9.30	10.00	0.70	0.07	0.20				
				11.40-12.00 20% quartz veining at 40 CA	37183		10.00	11.00	1.00	0.12	0.30				
					37184		11.00	12.00	1.00	0.12	0.10				
					37185		12.00	13.00	1.00	0.07	0.20				
					37186		13.00	14.00	1.00	0.07	0.20				
					37187		14.00	15.00	1.00	0.03	0.30				
					37188		15.00	16.00	1.00	0.06	0.30				
					37190	3	16.00	17.00	1.00	0.01	0.30				
17.00	30.20	FP	FP	light grey, fine grained groundmass with coarse grained white feldspar phenocrysts; sharp contact at 60 CA; 10% quartz veining at 60 CA	37191		17.00	18.00	1.00	0.01	0.10				
					37192		18.00	19.00	1.00	0.07	0.40				
					37193		19.00	20.00	1.00	0.01	0.50				
					37194		20.00	21.00	1.00	0.09	0.50				
					37195		21.00	22.00	1.00	0.10	0.10				
					37196		22.00	23.00	1.00	0.01	0.60				
					37197		23.00	24.00	1.00	0.03	0.60				
					37200		24.00	25.00	1.00	0.01	0.10				
					37201		25.00	26.00	1.00	0.11	0.60				
					37202		26.00	27.00	1.00	0.11	0.80				
					37203		27.00	28.00	1.00	0.04	0.70				
					37204		28.00	29.00	1.00	0.05	1.40				
					37205		29.00	30.20	1.20	0.02	0.30				
30.20	128.00	Siltstone	SILT	as above:	37206	1	30.20	31.00	0.80	0.02	0.60				
					37207	1	31.00	32.00	1.00	0.02	0.40				
					37208	1	32.00	33.00	1.00	0.01	0.50				
				81.30-89.30 argillaceous	37210	1	33.00	34.00	1.00	0.09	0.20				
					37211	1	34.00	35.00	1.00	0.04	0.20				
				121.0-128.0 argillaceous	37212	1	35.00	36.00	1.00	0.01	0.10				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
128.00	212.90	Greywacke	GWE	medium grey, fine grained, fairly massive; minor argillaceous material											
212.90	222.20	FP	FP	Feldspar Porphyry: light grey, fine grained, groundmass with fine grained white laths of feodspar; sharp contact at 10 and 80 CA											
222.20	230.80	Siltstone	SILT	as above:											
230.80	233.30	FP	FP	as above: chilled contact											
233.30	289.20	Siltstone	SILT	as above:											
				240.5-240.7 moderately sheared at 20 CA											
				240.7-242.8 argillaceous											
289.20	291.55	Mafic Dike	MAF	medium green-grey, fine grained massive, uniform; sharp contact at 20 and 80 CA	37213		320.00	321.00	1.00	0.01	0.20				
					37214		321.00	322.00	1.00	0.01	0.10				
					37215		322.00	323.00	1.00	0.01	0.10				
291.55	382.20	Siltstone	SILT	as above:	37216		323.00	324.00	1.00	0.10	0.10				
					37217		324.00	325.00	1.00	0.83	3.60				
				320.0-336.0 weak sericite alteration and brecciation	37220		325.00	326.00	1.00	0.01	0.10				
					37221		326.00	327.00	1.00	0.02	0.10				
					37222		327.00	328.00	1.00	0.04	0.10				
					37223		328.00	329.00	1.00	0.03	0.10				
					37224		329.00	330.00	1.00	0.03	0.10				
					37225		330.00	331.00	1.00	0.01	0.10				
					37226		331.00	332.00	1.00	0.01	0.20				
					37227		332.00	333.00	1.00	0.01	0.20				
					37228		333.00	334.00	1.00	0.01	0.10				
					37230		334.00	335.00	1.00	0.04	0.10				
					37231		335.00	336.00	1.00	0.01	0.20				
					37232		336.00	337.00	1.00	0.01	0.10				
					37233		337.00	338.00	1.00	0.01	0.20				
					37234		338.00	339.00	1.00	0.01	0.10				
				344.7 strong slip at 20 CA											
382.20	388.70	UMF Dike	UMF	dark greenish grey, medium grained, strongly foliated at 30 CA; talcose alteration; magnetic locally;											

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
				contact at 30 CA	37235		419.00	420.00	1.00	0.03	0.10				
					37236		420.00	420.40	0.40	0.11	0.40				
388.70	395.60	Siltstone	SILT	as above:	37237		420.40	421.00	0.60	0.08	0.50				
					37238		421.00	422.00	1.00	0.09	0.40				
395.60	401.20	UMF Dike	UMF	as above: contact at 40 CA	37239		422.00	423.00	1.00	0.05	0.30				
					37240		423.00	424.00	1.00	0.33	2.40				
401.20	420.40	Siltstone	SILT	as above: numerour quartz carbonate veining at 50 CA	37243		424.00	425.00	1.00	0.20	1.10				
					37244		425.00	425.30	0.30	0.94	5.30				
					37245	1	427.00	428.00	1.00	0.79	5.40				
420.40	425.30	Fault Zone	FZ	strongly sheared, brecciated at 40 CA; quartz carbonate veining at 40 CA	37246	1	428.00	429.00	1.00	0.04	0.20				
					37247	1	429.00	430.00	1.00	0.01	0.40				
425.30	471.60	Siltstone	SILT	as above:	37248	1	430.00	431.00	1.00	0.04	0.50				
					37249	1	431.00	432.00	1.00	0.04	0.70				
				427.0-434.0 1-2% disseminated pyrite	37250	1	432.00	433.00	1.00	0.10	0.80				
					37251	1	433.00	434.00	1.00	0.04	0.70				
				463.00-471.0 1-3% disseminated pyrite	37253	2	463.00	464.00	1.00	0.10	2.10				
					37254	2	464.00	465.00	1.00	0.04	0.80				
					37255	2	465.00	466.00	1.00	0.05	0.90				
					37256	2	466.00	467.00	1.00	0.01	0.40				
					37257	2	467.00	468.00	1.00	0.06	0.30				
					37258	2	468.00	469.00	1.00	0.09	0.70				
					37259	2	469.00	470.00	1.00	0.14	1129.30				
					37260	2	470.00	471.00	1.00	0.18	1.30				
471.60	474.70	CGL	CGL	light to medium grey, pebbles of siltstone; 3-5% disseminated pyrite	37263	2	471.00	471.60	0.60	0.04	0.50				
					37264	5	471.60	472.00	0.40	0.11	0.60				
					37265	4	472.00	473.00	1.00	0.11	0.60				
					37266	4	473.00	474.00	1.00	0.09	0.70				
					37267	5	474.00	474.70	0.70	0.08	0.40				
474.70	503.50	Siltstone	SILT	as above:	37268	3	474.70	475.00	0.30	0.05	0.60				
					37269	3	475.00	476.00	1.00	0.07	0.60				
					37270	3	476.00	477.00	1.00	0.09	0.70				
				478.8-479.0 pink quartz carbonate breccia at 20 CA	37271	2	477.00	478.00	1.00	0.08	0.60				
					37273	2	478.00	479.00	1.00	0.05	0.20				
					37274	2	479.00	480.00	1.00	0.07	0.10				
					37275	2	480.00	481.00	1.00	0.05	0.10				
					37276	2	481.00	482.00	1.00	0.06	0.20				
					37277	2	482.00	483.00	1.00	0.04	0.20				
					37278	2	483.00	484.00	1.00	0.03	0.10				
					37279	2	484.00	485.00	1.00	0.06	0.20				
					37280	2	485.00	486.00	1.00	0.01	0.20				
					37283	1	500.00	501.00	1.00	0.02	0.10				
					37284	1	501.00	502.00	1.00	0.01	0.10				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					37285	1	502.00	503.00	1.00	0.02	0.10				
					37286	1	503.00	504.00	1.00	0.01	0.10				
503.50	508.50	FP	FP	medium grey, fine grained white feldspar phenocrysts in a fine grained groundmass; contact at 40 CA; 1% py	37287	1	504.00	505.00	1.00	0.01	0.10				
					37288	1	505.00	506.00	1.00	0.03	0.10				
					37289	1	506.00	507.00	1.00	0.05	0.10				
508.50	520.45	Diabase	DIA	dark grey green, medium grained, massive uniform, ophitic texture, magnetic; contact at 50 and 70 CA	37290	1	507.00	508.00	1.00	0.01	0.10				
					37291	1	508.00	508.50	0.50	0.08	0.10				
					37293	1	520.45	521.00	0.55	0.23	0.10				
520.45	523.57	FP	FP	as above: 1% disseminated pyrite	37294	1	521.00	522.00	1.00	0.12	0.10				
					37295	1	522.00	523.00	1.00	0.01	0.10				
523.57	523.70	Fault Zone	FZ	strongly sheared at 70 CA; fibrous asbestos	37296	1	523.00	523.57	0.57	0.02	0.10				
523.70	597.00	Diabasae	DIA	as above: 580.6-581.0 quartz carbonate slip at 40 CA; trace cpy,py											
				EOH											
				core stored at Matachewan											
Downhole Tests:															
	Depth	AZ	DIP												
	50	144.3	-59.8												
	100	145.4	-59.8												
	201	142	-59.4												
	252	146.3	-59.4												
	351	146.9	-58.5												
	402	151	-58.1												
	450	156.1	-56.8												
	504	156.5	-56.5												
	550	153.1	-55.5												
	600	165.7	-55.4												

Opawica Explorations Inc.

Matachewan
DDH#: OPW-07-004
Az and Dip: 330/-60
E.O.H: 600 m

GRID LOCATION: Powell Twp., Ontario
GRID: OPW: 4E 15+00S
UTM, type: 0522879E, 5311733N: Nad: 83 Zone: 17
Elev.:

Claim: MR37455, 511486
Drill Company: Downing: NQ Core
Start: July 06, 2007; End: July 14, 2007
Logged by: Fred Sharpley

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
0.00	2.10		OVB												
2.10	31.18	SILTSTONE	SILT	light grey, fine grained, weakly banded at 30 CA; auto-brecciated; 1-3% disseminated pyrite, fine to medium grained	34916	1	2.10	3.00	0.90	0.01	0.20				
					34917	1	3.00	4.00	1.00	0.01	0.10				
					34918	1	4.00	5.00	1.00	0.01	0.70				
					34919	1	5.00	6.00	1.00	0.01	0.70				
					34920	1	6.00	7.00	1.00	0.03	0.40				
					34921	1	7.00	8.00	1.00	0.02	0.70				
					34922	1	8.00	9.00	1.00	0.04	0.40				
					34923	1	9.00	10.00	1.00	0.01	0.20				
					34924	1	10.00	11.00	1.00	0.01	0.10				
					34925	1	11.00	12.00	1.00	0.01	0.30				
					34927	2	12.00	13.00	1.00	0.01	0.10				
				12.50 - 20.00 autobrecciated, 2-3% disseminated pyrite	34928	2	13.00	14.00	1.00	0.02	0.60				
					34929	3	14.00	15.00	1.00	0.01	0.90				
					34930	3	15.00	16.00	1.00	0.01	0.10				
					34931	3	16.00	17.00	1.00	0.01	0.10				
					34932	3	17.00	18.00	1.00	0.01	0.10				
					34933	3	18.00	19.00	1.00	0.01	0.10				
					34934	3	19.00	20.00	1.00	0.01	0.10				
					34937	2	20.00	21.00	1.00	0.01	0.10				
					34938	3	21.00	22.00	1.00	0.02	0.10				
					34939	3	22.00	23.00	1.00	0.01	0.20				
					34940	3	23.00	24.00	1.00	0.02	0.10				
					34941	3	24.00	25.00	1.00	0.01	0.10				
					34942	2	25.00	26.00	1.00	0.02	0.10				
					34943	2	26.00	27.00	1.00	0.01	0.10				
					34944	2	27.00	28.00	1.00	0.01	0.10				
					34945	2	28.00	29.00	1.00	0.01	0.10				
					34947	3	29.00	30.00	1.00	0.01	0.30				
					34948	3	30.00	31.00	1.00	0.01	0.70				
31.18	32.54	LAM	LAM	LAMPROPHYRE DIKE: dark green, fine grained, massive uniform, sharp contact at 60 CA	34949	5	31.00	32.00	1.00	0.02	1.50				
					34950	5	32.00	33.00	1.00	0.01	0.60				
32.54	42.10	SILTSTONE	SILT	as above: weakly banded at 30 CA	34951	2	33.00	34.00	1.00	0.01	0.10				
					34952	2	34.00	35.00	1.00	0.01	0.10				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					34953	2	35.00	36.00	1.00	0.01	0.10				
					34954	2	36.00	37.00	1.00	0.01	0.10				
					34957	2	37.00	38.00	1.00	0.01	0.10				
					34958	2	38.00	39.00	1.00	0.01	0.10				
					34959	2	39.00	40.00	1.00	0.01	0.10				
					34960	2	40.00	41.00	1.00	0.01	0.10				
					34961	2	41.00	42.00	1.00	0.01	0.20				
					34962	5	42.00	43.00	1.00	0.01	1.00				
42.10	43.00	LAM	LAM	as above: strong disseminated pyrite	34963	2	43.00	44.00	1.00	0.01	0.50				
					34964	2	44.00	45.00	1.00	0.01	0.10				
43.00	60.45	SILTSTONE	SILT	as above	34965	2	45.00	46.00	1.00	0.01	0.10				
					34967	2	46.00	47.00	1.00	0.01	0.10				
					34968	2	47.00	48.00	1.00	0.01	0.10				
					34969	2	48.00	49.00	1.00	0.01	0.10				
					34970	2	49.00	50.00	1.00	0.01	0.10				
					34971	2	50.00	51.00	1.00	0.02	0.20				
					34972	2	51.00	52.00	1.00	0.01	0.10				
					34973	2	52.00	53.00	1.00	0.01	0.10				
					34974	2	53.00	54.00	1.00	0.02	0.10				
					34977	2	54.00	55.00	1.00	0.03	0.10				
					34978	2	55.00	56.00	1.00	0.04	0.20				
					34979	2	56.00	57.00	1.00	0.03	0.10				
					34980	2	57.00	58.00	1.00	0.03	0.10				
					34981	2	58.00	59.00	1.00	0.01	0.10				
					34982	2	59.00	60.00	1.00	0.04	0.10				
60.45	62.30	LAM	LAM	as above: sharp contact at 50 CA	34983	4	60.00	61.00	1.00	0.04	0.40				
					34984	5	61.00	62.00	1.00	0.05	0.40				
62.30	69.30	SILTSTONE	SILT	as above: weakly banded at 40 CA	34985	2	62.00	63.00	1.00	0.01	0.20				
					34987	2	63.00	64.00	1.00	0.01	0.10				
69.30	73.60	DIABASE	DIA	dark-grey, fine grained massive, uniform, ophitic texture	34988	2	64.00	65.00	1.00	0.02	0.10				
				69.6 - 69.9 quartz vein at 30 CA	34989	2	65.00	66.00	1.00	0.01	0.20				
				70.90- 71.10 quartz vein at 50 CA	34990	2	66.00	67.00	1.00	0.08	0.10				
					34991	2	67.00	68.00	1.00	0.05	0.20				
					34992	2	68.00	69.00	1.00	0.01	0.40				
					34993		69.00	70.00	1.00	0.01	0.20				
					34994		70.00	71.00	1.00	0.01	0.10				
73.60	87.20	SILTSTONE	SILT	as above: sharp contact at 70 CA	34997		71.00	72.00	1.00	0.01	0.20				
					34998		72.00	73.00	1.00	0.01	0.20				
					34999	3	73.00	74.00	1.00	0.01	0.10				
					35000	4	74.00	75.00	1.00	0.04	0.20				
					35501	4	75.00	76.00	1.00	0.04	0.10				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					35502	2	76.00	77.00	1.00	0.03	0.10				
					35503	2	77.00	78.00	1.00	0.04	0.10				
					35504	2	78.00	79.00	1.00	0.01	0.10				
					35505	2	79.00	80.00	1.00	0.03	0.10				
					35507	2	80.00	81.00	1.00	0.02	0.10				
					35508	2	81.00	82.00	1.00	0.03	0.10				
					35509	2	82.00	83.00	1.00	0.08	0.10				
					35510	2	83.00	84.00	1.00	0.16	0.10				
					35511	4	84.00	85.00	1.00	0.06	0.10				
					35512	4	85.00	86.00	1.00	0.11	0.10				
87.20	92.65	DIABASE	DIA	as above:	35513	4	86.00	87.00	1.00	0.11	0.20				
					35514	2	87.00	88.00	1.00	0.06	0.10				
					35517		88.00	89.00	1.00	0.01	0.10				
					35518	2	89.00	90.00	1.00	0.04	0.10				
					35519	4	90.00	91.00	1.00	0.08	0.10				
					35520	2	91.00	92.00	1.00	0.01	0.10				
					35521	2	92.00	93.00	1.00	0.01	0.10				
92.65	97.50	SILTSTONE	SILT	as above	35522	4	93.00	94.00	1.00	0.04	0.10				
					35523	2	94.00	95.00	1.00	0.01	0.10				
					35524	4	95.00	96.00	1.00	0.02	0.10				
					35525	4	96.00	97.00	1.00	0.01	0.10				
					35527	3	97.00	98.00	1.00	0.02	0.10				
					35528	3	98.00	99.00	1.00	0.01	0.10				
97.50	111.55	DIABASE	DIA	as above:	35529	3	99.00	100.00	1.00	0.01	0.10				
					35530	2	100.00	101.00	1.00	0.04	0.10				
					35531	2	101.00	102.00	1.00	0.02	0.10				
					35532	2	102.00	103.00	1.00	0.01	0.10				
				101.00 - 101.10 quartz vein at 50 CA	35533	3	111.00	111.55	0.55	0.01	0.20				
					35534	3	111.55	112.00	0.45	0.01	0.10				
					35537	3	112.00	113.00	1.00	0.01	0.10				
					35538	3	113.00	114.00	1.00	0.02	0.30				
111.55	234.30	CGL	CGL	Contact Breccia Zone: medium to dark grey-green, mixed diabase and siltstone; xenoliths of dabase and siltstone; 1-3% disseminated pyrite; pebbles of syenite, siltstone, diabase	35539	3	114.00	115.00	1.00	0.01	0.10				
					35540	3	115.00	116.00	1.00	0.01	0.10				
					35541	3	116.00	117.00	1.00	0.02	0.10				
					35542	3	117.00	118.00	1.00	0.02	0.10				
					35543	3	118.00	119.00	1.00	0.03	0.20				
					35544	3	119.00	120.00	1.00	0.03	0.10				
					35545	3	120.00	121.00	1.00	0.01	0.10				
					35547	3	121.00	122.00	1.00	0.01	0.10				
					35548	3	122.00	123.00	1.00	0.01	0.10				
					35549	3	123.00	124.00	1.00	0.01	0.30				
					35550	3	124.00	125.00	1.00	0.01	0.20				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					35551	3	125.00	126.00	1.00	0.02	0.30				
					35552	3	126.00	127.00	1.00	0.01	0.20				
					35553	3	127.00	128.00	1.00	0.01	0.40				
					35554	3	128.00	129.00	1.00	0.01	0.40				
					35557	3	129.00	130.00	1.00	0.01	0.10				
					35558	3	130.00	131.00	1.00	0.01	0.10				
					35559	3	131.00	132.00	1.00	0.01	0.30				
					35560	3	132.00	133.00	1.00	0.01	0.80				
					35561	3	133.00	134.00	1.00	0.01	0.10				
					35562	3	134.00	135.00	1.00	0.01	0.20				
					35563	3	135.00	136.00	1.00	0.01	0.10				
					35564	3	136.00	137.00	1.00	0.01	0.10				
					35565	3	137.00	138.00	1.00	0.01	0.10				
					35567	3	138.00	139.00	1.00	0.01	0.10				
					35568	3	139.00	140.00	1.00	0.01	0.20				
					35569	3	140.00	141.00	1.00	0.01	0.20				
					35570	3	141.00	142.00	1.00	0.01	0.20				
					35571	3	142.00	143.00	1.00	0.01	0.10				
					35572	3	143.00	144.00	1.00	0.01	0.10				
					35573	3	144.00	145.00	1.00	0.01	0.10				
					35574	3	145.00	146.00	1.00	0.01	0.20				
					35577	3	146.00	147.00	1.00	0.01	0.10				
					35578	3	147.00	148.00	1.00	0.01	0.10				
					35579	3	148.00	149.00	1.00	0.01	0.10				
					35580	3	149.00	150.00	1.00	0.01	0.20				
					35581	3	150.00	151.00	1.00	0.01	0.20				
					35582	3	151.00	152.00	1.00	0.01	0.10				
					35583	3	152.00	153.00	1.00	0.01	0.10				
					35584	3	153.00	154.00	1.00	0.01	0.10				
					35585	3	154.00	155.00	1.00	0.01	0.10				
					35587	3	155.00	156.00	1.00	0.01	0.10				
					35588	3	156.00	157.00	1.00	0.01	0.10				
					35589	3	157.00	158.00	1.00	0.01	0.10				
					35590	3	158.00	159.00	1.00	0.01	0.10				
					35591	3	159.00	160.00	1.00	0.01	0.10				
					35592	3	160.00	161.00	1.00	0.01	0.10				
					35593	3	161.00	162.00	1.00	0.01	0.10				
					35594	3	162.00	163.00	1.00	0.01	0.10				
					35597	3	163.00	164.00	1.00	0.01	0.10				
					35598	3	164.00	165.00	1.00	0.01	0.10				
					35599	3	165.00	166.00	1.00	0.01	0.10				
					35600	3	166.00	167.00	1.00	0.01	0.10				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					35601	3	167.00	168.00	1.00	0.02	0.10				
					35602	3	168.00	169.00	1.00	0.01	0.10				
					35603	3	169.00	170.00	1.00	0.01	0.10				
					35604	3	170.00	171.00	1.00	0.01	0.10				
					35605	3	171.00	172.00	1.00	0.01	0.10				
					35607	2	172.00	173.00	1.00	0.01	0.10				
					35608	2	173.00	174.00	1.00	0.01	0.10				
					35609	2	174.00	175.00	1.00	0.01	0.80				
					35610	2	175.00	176.00	1.00	0.01	0.40				
					35611	2	176.00	177.00	1.00	0.01	0.40				
				177.10- 3 cm pink quartz-carbonate vein at 30 CA	35612	2	177.00	178.00	1.00	0.01	0.20				
					35613	2	178.00	179.00	1.00	0.01	0.10				
					35614	2	179.00	180.00	1.00	0.01	0.30				
					35617	2	180.00	181.00	1.00	0.01	0.20				
					35618	2	181.00	182.00	1.00	0.01	0.10				
					35619	2	182.00	183.00	1.00	0.01	0.10				
					35620	2	183.00	184.00	1.00	0.01	0.10				
					35621	2	184.00	185.00	1.00	0.01	0.20				
					35622	2	185.00	186.00	1.00	0.01	0.20				
					35623	2	186.00	187.00	1.00	0.01	0.30				
					35624	2	187.00	188.00	1.00	0.01	0.40				
					35625	2	188.00	189.00	1.00	0.01	0.10				
					35627	2	189.00	190.00	1.00	0.01	0.10				
					35628	2	190.00	191.00	1.00	0.01	0.10				
					35629	2	191.00	192.00	1.00	0.01	0.10				
					35630	2	192.00	193.00	1.00	0.01	0.10				
					35631	2	193.00	194.00	1.00	0.01	0.10				
					35632	2	194.00	195.00	1.00	0.01	0.20				
					35633	2	195.00	196.00	1.00	0.01	0.10				
					35634	2	196.00	197.00	1.00	0.01	0.10				
				196.96- 5 cm QUARTZ CARBONATE VEIN AT 75 CA	35637	2	197.00	198.00	1.00	0.01	0.10				
					35638	2	198.00	199.00	1.00	0.01	0.10				
					35639	2	199.00	200.00	1.00	0.01	0.10				
					35640	2	200.00	201.00	1.00	0.02	0.10				
					35641	2	201.00	202.00	1.00	0.01	0.10				
					35642	2	202.00	203.00	1.00	0.01	0.10				
					35643	2	203.00	204.00	1.00	0.01	0.10				
					35644	2	204.00	205.00	1.00	0.01	0.10				
					35645	2	205.00	206.00	1.00	0.01	0.20				
					35647	2	206.00	207.00	1.00	0.01	0.10				
				207.64 - 208.4 Mafic Dike: medium green, fine-grained, massive, uniform; strong disseminated pyrite	35648	3	207.00	208.00	1.00	0.01	0.20				
					35649	4	208.00	209.00	1.00	0.01	0.30				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					35650	2	209.00	210.00	1.00	0.01	0.10				
					35651	2	210.00	211.00	1.00	0.01	0.70				
					35652	5	211.00	212.00	1.00	0.01	1.10				
					35653	5	212.00	213.00	1.00	0.01	1.40				
					35654	2	213.00	214.00	1.00	0.01	0.10				
					35657	2	214.00	215.00	1.00	0.01	0.40				
					35658	2	215.00	216.00	1.00	0.01	0.40				
					35659	2	216.00	217.00	1.00	0.01	0.30				
					35660	2	217.00	218.00	1.00	0.01	0.40				
					35661	2	218.00	219.00	1.00	0.01	0.30				
					35662	2	219.00	220.00	1.00	0.01	0.10				
					35663	2	220.00	221.00	1.00	0.01	0.10				
					35664	2	221.00	222.00	1.00	0.01	0.10				
					35665	2	222.00	223.00	1.00	0.01	0.10				
					35667	2	223.00	224.00	1.00	0.01	0.10				
					35668	2	224.00	225.00	1.00	0.01	0.10				
					35669	2	225.00	226.00	1.00	0.01	0.10				
					35670	2	226.00	227.00	1.00	0.01	0.10				
					35671	2	227.00	228.00	1.00	0.01	0.10				
					35672	2	228.00	229.00	1.00	0.01	0.10				
					35673	2	229.00	230.00	1.00	0.01	0.10				
					35674	5	230.00	231.00	1.00	0.05	0.10				
				230.0 - 234.30 core broken-up, numerous chlorite slips at 20 CA	35677	5	231.00	232.00	1.00	0.03	0.20				
					35678	5	232.00	233.00	1.00	0.02	0.10				
					35679	5	233.00	234.30	1.30	0.01	0.10				
234.30	238.40	SYENITE	SYN	234.30 - 238.40 strongly hematized, reddis color; strong disseminated pyrite; pink, fine grained, massive, uniform,	35680	2	234.30	235.00	0.70	0.01	0.10				
					35681	2	235.00	236.00	1.00	0.01	0.10				
					35682	2	236.00	237.00	1.00	0.02	0.10				
					35683	2	237.00	238.00	1.00	0.01	0.10				
238.40	243.35	LAM	LAM	as above: contact at 70 CA	35684	2	238.00	239.00	1.00	0.01	0.10				
					35685	2	239.00	240.00	1.00	0.01	0.10				
					35687	2	240.00	241.00	1.00	0.01	0.10				
					35688	2	241.00	242.00	1.00	0.01	0.10				
					35689	2	242.00	243.00	1.00	0.01	0.10				
					35690	2	243.00	244.00	1.00	0.01	0.10				
243.35	253.00	CGL	CGL	as above: 1-3% disseminated pyrite	35691	2	244.00	245.00	1.00	0.01	0.10				
					35692	2	245.00	246.00	1.00	0.01	0.10				
					35693	2	246.00	247.00	1.00	0.01	0.10				
					35694	2	247.00	248.00	1.00	0.01	0.10				
					35697	2	248.00	249.00	1.00	0.01	0.10				
					35698	2	249.00	250.00	1.00	0.01	0.10				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					35699	2	250.00	251.00	1.00	0.01	0.10				
					35700	2	251.00	252.00	1.00	0.01	0.10				
					35701	2	252.00	253.00	1.00	0.01	0.10				
253.00	307.00	SILTSTONE	SILT	Conglomeritic Siltstone: fewer pebbles; 1-3% disseminated pyrite; very weak bedding; possibly greywacke.	35702	2	253.00	254.00	1.00	0.01	0.10				
					35703	2	254.00	255.00	1.00	0.02	0.10				
					35704	2	255.00	256.00	1.00	0.01	0.20				
					35705	2	256.00	257.00	1.00	0.01	0.30				
					35707	2	257.00	258.00	1.00	0.02	0.10				
					35708	2	258.00	259.00	1.00	0.01	0.10				
					35709	2	259.00	260.00	1.00	0.02	0.10				
					35710	2	260.00	261.00	1.00	0.01	0.10				
					35711	2	261.00	262.00	1.00	0.01	0.10				
					35712	2	262.00	263.00	1.00	0.01	0.10				
					35713	2	263.00	264.00	1.00	0.01	0.10				
					35714	2	264.00	265.00	1.00	0.01	0.10				
					35717	2	265.00	266.00	1.00	0.01	0.10				
					35718	2	266.00	267.00	1.00	0.03	0.10				
					35719	2	267.00	268.00	1.00	0.03	0.20				
					35720	2	268.00	269.00	1.00	0.02	0.10				
					35721	2	269.00	270.00	1.00	0.01	0.10				
					35722	2	270.00	271.00	1.00	0.01	0.10				
					35723	2	271.00	272.00	1.00	0.01	0.10				
					35724	2	272.00	273.00	1.00	0.01	0.10				
					35725	2	273.00	274.00	1.00	0.01	0.10				
					35727	2	274.00	275.00	1.00	0.01	0.10				
					35728	2	275.00	276.00	1.00	0.01	0.10				
					35729	2	276.00	277.00	1.00	0.01	0.20				
					35730	2	277.00	278.00	1.00	0.01	0.10				
					35731	2	278.00	279.00	1.00	0.01	0.10				
					35732	2	279.00	280.00	1.00	0.01	0.20				
					35733	2	280.00	281.00	1.00	0.01	0.20				
					35734	2	281.00	282.00	1.00	0.01	0.20				
					35737	2	282.00	283.00	1.00	0.01	0.10				
					35738	2	283.00	284.00	1.00	0.02	0.10				
					35739	2	284.00	285.00	1.00	0.01	0.10				
					35740	2	285.00	286.00	1.00	0.01	0.10				
					35741	2	286.00	287.00	1.00	0.01	0.10				
					35742	2	287.00	288.00	1.00	0.01	0.10				
					35743	2	288.00	289.00	1.00	0.01	0.10				
					35744	2	289.00	290.00	1.00	0.01	0.10				
					35745	2	290.00	291.00	1.00	0.01	0.10				
					35747	2	291.00	292.00	1.00	0.01	0.10				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					35748	2	292.00	293.00	1.00	0.02	0.10				
					35749	2	293.00	294.00	1.00	0.02	0.20				
					35750	2	294.00	295.00	1.00	0.01	0.10				
					35751	2	295.00	296.00	1.00	0.01	0.10				
					35752	2	296.00	297.00	1.00	0.01	0.20				
					35753	2	297.00	298.00	1.00	0.01	0.40				
					35754	2	298.00	299.00	1.00	0.01	0.40				
					35757	2	299.00	300.00	1.00	0.02	0.30				
					35758	2	300.00	301.00	1.00	0.01	0.10				
					35759	2	301.00	302.00	1.00	0.01	0.10				
					35760	2	302.00	303.00	1.00	0.01	0.10				
					35761	2	303.00	304.00	1.00	0.01	0.10				
					35762	2	304.00	305.00	1.00	0.01	0.10				
					35763	2	305.00	306.00	1.00	0.01	0.10				
					35764	2	306.00	307.00	1.00	0.01	0.10				
307.00	348.00	Greywacke	GW	medium to dark grey, poorly sorted, poorly banded locally at 50 CA; cobbles of siltstone, greenstone locally < 4 cm	35765	2	307.00	308.00	1.00	0.01	0.10				
				1-2% disseminated pyrite; minor quartz carbonate veins	35767	2	308.00	309.00	1.00	0.02	0.10				
				at 20 and 40 CA; conglomeritic greywacke	35768	2	309.00	310.00	1.00	0.01	0.10				
					35769	2	310.00	311.00	1.00	0.01	0.10				
					35770	2	311.00	312.00	1.00	0.01	0.10				
					35771	2	312.00	313.00	1.00	0.03	0.10				
					35772	2	313.00	314.00	1.00	0.01	0.10				
					35773	2	314.00	315.00	1.00	0.01	0.10				
					35774	2	315.00	316.00	1.00	0.01	0.10				
					35777	2	316.00	317.00	1.00	0.02	0.10				
					35778	2	317.00	318.00	1.00	0.01	0.10				
					35779	2	318.00	319.00	1.00	0.01	0.10				
					35780	2	319.00	320.00	1.00	0.01	0.10				
					35781	2	320.00	321.00	1.00	0.01	0.10				
					35782	2	321.00	322.00	1.00	0.01	0.10				
					35783	2	322.00	323.00	1.00	0.01	0.10				
					35784	2	323.00	324.00	1.00	0.01	0.10				
					35785	2	324.00	325.00	1.00	0.01	0.10				
					35787	2	325.00	326.00	1.00	0.03	0.10				
					35788	2	326.00	327.00	1.00	0.01	0.10				
					35789	2	327.00	328.00	1.00	0.01	0.10				
					35790	2	328.00	329.00	1.00	0.01	0.10				
					35791	2	329.00	330.00	1.00	0.01	0.10				
					35792	2	330.00	331.00	1.00	0.01	0.10				
					35793	2	331.00	332.00	1.00	0.01	0.10				
					35794	2	332.00	333.00	1.00	0.01	0.10				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					35797	2	333.00	334.00	1.00	0.01	0.10				
					35798	2	334.00	335.00	1.00	0.01	0.20				
					35799	2	335.00	336.00	1.00	0.01	0.10				
					35800	2	336.00	337.00	1.00	0.01	0.30				
					35801	2	337.00	338.00	1.00	0.01	0.10				
					35802	2	338.00	339.00	1.00	0.01	0.10				
					35803	2	339.00	340.00	1.00	0.01	0.10				
					35804	2	340.00	341.00	1.00	0.01	0.10				
					35805	2	341.00	342.00	1.00	0.01	0.20				
					35807	2	342.00	343.00	1.00	0.01	0.20				
					35808	2	343.00	344.00	1.00	0.01	0.10				
					35809	2	344.00	345.00	1.00	0.01	0.10				
					35810	2	345.00	346.00	1.00	0.01	0.10				
					35811	2	346.00	347.00	1.00	0.02	0.20				
					35812	2	347.00	348.00	1.00	0.10	0.10				
348.00	348.70	Fault Zone	FZ	dark green, strongly sheared at 60 CA; strongly chloritized; 5% disseminated fine pyrite	35813	2	348.00	348.70	1.00	0.16	0.40				
				351.05 - 351.80 Lamprophyre Dike: contact at 40-50 CA	35814	2	348.70	350.00	1.30	0.05	0.10				
348.70	356.00	Greywacke	GW	as above: conglomeratic	35817	2	350.00	351.00	1.00	0.01	0.10				
					35818	2	351.00	352.00	1.00	0.01	0.10				
					35819	2	352.00	353.00	1.00	0.01	0.10				
					35820	2	353.00	354.00	1.00	0.01	0.10				
					35821	2	354.00	355.00	1.00	0.03	0.10				
					35822	2	355.00	356.00	1.00	0.01	0.10				
356.00	366.60	Greywacke	GW	Alteration Zone: strong hematite alteration; 3-5% disseminated fine pyrite, 3-5%; conglomeratic	35823	3	356.00	357.00	1.00	0.07	0.10				
					35824	3	357.00	358.00	1.00	0.05	0.10				
					35825	3	358.00	359.00	1.00	0.03	0.10				
					35827	3	359.00	360.00	1.00	0.01	0.10				
					35828	3	360.00	361.00	1.00	0.02	0.10				
					35829	3	361.00	362.00	1.00	0.01	0.10				
					35830	3	362.00	363.00	1.00	0.01	0.10				
					35831	3	363.00	364.00	1.00	0.01	0.10				
					35832	3	364.00	365.00	1.00	0.01	0.10				
					35833	3	365.00	366.00	1.00	0.01	0.10				
					35834	4	366.00	366.60	0.60	0.01	0.10				
366.60	387.90	Greywacke	GW	Alteration Zone: strong sericite alteration; 3-5% disseminated pyrite, fine-grained; conglomeratic; whitish color.	35837	4	366.60	368.00	1.40	0.01	0.10				
					35838	4	368.00	369.00	1.00	0.01	0.10				
					35839	4	369.00	370.00	1.00	0.01	0.10				
					35840	4	370.00	371.00	1.00	0.01	0.10				
					35841	4	371.00	372.00	1.00	0.02	0.10				
					35842	4	372.00	373.00	1.00	0.01	0.10				
					35843	4	373.00	374.00	1.00	0.03	0.10				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					35844	4	374.00	375.00	1.00	0.01	0.10				
					35845	4	375.00	376.00	1.00	0.02	0.10				
					35847	4	376.00	377.00	1.00	0.01	0.10				
					35848	4	377.00	378.00	1.00	0.01	0.10				
					35849	4	378.00	379.00	1.00	0.01	0.10				
					35850	4	379.00	380.00	1.00	0.01	0.10				
					35851	4	380.00	381.00	1.00	0.02	0.10				
					35852	4	381.00	382.00	1.00	0.01	0.10				
					35853	4	382.00	383.00	1.00	0.01	0.10				
					35854	4	383.00	384.00	1.00	0.02	0.10				
					35857	4	384.00	385.00	1.00	0.02	0.10				
					35858	4	385.00	386.00	1.00	0.03	0.10				
					35859	4	386.00	387.00	1.00	0.01	0.10				
					35860	4	387.00	387.90	0.90	0.06	0.40				
387.90	408.00	Greywacke	GW	as above: conglomeratic; 3-5% disseminated pyrite	35861	4	387.90	389.00	1.10	0.05	0.10				
					35862	4	389.00	390.00	1.00	0.15	1.10				
					35863	4	390.00	391.00	1.00	0.08	0.30				
					35864	4	391.00	392.00	1.00	0.21	0.10				
					35865	4	392.00	393.00	1.00	0.01	0.10				
					35867	3	393.00	394.00	1.00	0.01	0.10				
					35868	3	394.00	395.00	1.00	0.01	0.10				
				394.90 - 395.86 Diorite Dike: dark green-grey, fine-frained massive, sharp contact at 30 CA	35869	3	395.00	396.00	1.00	0.01	0.40				
					35870	3	396.00	397.00	1.00	0.01	0.10				
					35871	3	397.00	398.00	1.00	0.03	0.30				
					35872	3	398.00	399.00	1.00	0.01	0.10				
					35873	3	399.00	400.00	1.00	0.03	0.10				
					35874	3	400.00	401.00	1.00	0.01	0.10				
					35877	3	401.00	402.00	1.00	0.03	0.10				
					35878	3	402.00	403.00	1.00	0.09	0.10				
					35879	3	403.00	404.00	1.00	0.01	0.10				
					35880	3	404.00	405.00	1.00	0.02	0.10				
					35881	3	405.00	406.00	1.00	0.01	0.10				
					35882	3	406.00	407.00	1.00	0.05	0.10				
					35883	3	407.00	408.00	1.00	0.01	0.30				
408.00	432.50	CGL	CGL	as above: 2-3% disseminated pyrite, fine	35884	3	408.00	409.00	1.00	0.06	0.10				
					35886	3	409.00	410.00	1.00	0.01	0.10				
					35887	3	410.00	411.00	1.00	0.01	0.20				
					35888	3	411.00	412.00	1.00	0.45	0.10				
					35889	3	412.00	413.00	1.00	0.01	0.10				
					35890	3	413.00	414.00	1.00	0.01	0.10				
					35891	3	414.00	415.00	1.00	0.01	0.10				
					35892	3	415.00	416.00	1.00	0.03	0.10				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					35893	3	416.00	417.00	1.00	0.03	0.10				
					35896	3	417.00	418.00	1.00	0.34	0.10				
					35897	3	418.00	419.00	1.00	0.02	0.10				
					35898	3	419.00	420.00	1.00	0.02	0.10				
					35899	3	420.00	421.00	1.00	0.05	0.10				
					35900	3	421.00	422.00	1.00	0.30	0.10				
					35901	3	422.00	423.00	1.00	0.15	0.10				
					35902	3	423.00	424.00	1.00	0.20	0.20				
					35903	3	424.00	425.00	1.00	0.18	0.20				
					35904	3	425.00	426.00	1.00	0.32	0.10				
					35906	3	426.00	427.00	1.00	0.22	0.10				
					35907	3	427.00	428.00	1.00	0.05	0.10				
					35908	3	428.00	429.00	1.00	0.02	0.10				
					35909	3	429.00	430.00	1.00	0.01	0.10				
					35910	3	430.00	431.00	1.00	0.01	0.10				
					35911	3	431.00	432.00	1.00	0.01	0.20				
432.50	444.70	Diabase	DIA	black color, very fine grained, foliated at 40-50 CA;	35912	2	432.00	433.00	1.00	0.01	0.10				
				fine grained massive, sharp contact at 50 CA	35913	2	433.00	434.00	1.00	0.02	0.20				
					35916	2	444.70	445.00	0.30	0.25	0.20				
444.70	480.40	CGL	CGL	as above: 1-3% disseminated pyrite	35917	2	445.00	446.00	1.00	0.09	0.10				
					35918	2	446.00	447.00	1.00	0.04	0.10				
					35919	2	447.00	448.00	1.00	0.02	0.10				
					35920	2	448.00	449.00	1.00	0.02	0.10				
					35921	2	449.00	450.00	1.00	0.03	0.10				
					35922	2	450.00	451.00	1.00	0.02	0.10				
					35923	2	451.00	452.00	1.00	0.05	0.10				
					35924	3	452.00	453.00	1.00	0.01	0.10				
					35926	3	453.00	454.00	1.00	0.02	0.10				
					35927	3	454.00	455.00	1.00	0.01	0.10				
					35928	2	455.00	456.00	1.00	0.04	0.10				
					35929	2	456.00	457.00	1.00	0.02	0.10				
					35930	2	457.00	458.00	1.00	0.11	0.10				
					35931	2	458.00	459.00	1.00	0.01	0.30				
					35932	2	459.00	460.00	1.00	0.02	0.10				
					35933	2	460.00	461.00	1.00	0.03	0.10				
					35936	2	461.00	462.00	1.00	0.01	0.10				
					35937	1	462.00	463.00	1.00	0.02	0.10				
					35938	1	463.00	464.00	1.00	0.02	0.10				
					35939	1	464.00	465.00	1.00	0.01	0.10				
					35940	1	465.00	466.00	1.00	0.01	0.10				
					35941	1	466.00	467.00	1.00	0.15	0.10				
					35942	1	467.00	468.00	1.00	0.03	0.10				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					35943	1	468.00	469.00	1.00	0.01	0.10				
					35944	1	469.00	470.00	1.00	0.02	0.10				
					35946	1	470.00	471.00	1.00	0.04	0.10				
					35947	1	471.00	472.00	1.00	0.01	0.10				
					35948	1	472.00	473.00	1.00	0.01	0.10				
					35949	1	473.00	474.00	1.00	0.01	0.10				
					35950	1	474.00	475.00	1.00	0.01	0.10				
					35951	1	475.00	476.00	1.00	0.01	0.10				
					35952	1	476.00	477.00	1.00	0.01	0.10				
					35953	1	477.00	478.00	1.00	0.08	0.10				
					35956	1	478.00	479.00	1.00	0.01	0.10				
					35957	1	479.00	480.00	1.00	0.01	0.10				
					35958	1	480.00	480.40	0.40	0.01	0.10				
480.40	483.55	Diorite	DIO	Diorite Dike: dark green, fine grained, massive uniform sharp contact at 50 CA; 70% diorite-30% hematized conglomrate.	35959		480.40	481.00	0.60	0.01	0.10				
					35960		481.00	482.00	1.00	0.04	0.10				
					35961		482.00	483.00	1.00	0.02	0.10				
					35962		483.00	483.55	0.55	0.01	0.10				
483.55	490.60	CGL	CGL	Hematized Conglomerate:	35963	1	483.55	484.00	0.45	0.01	0.40				
					35964	1	484.00	485.00	1.00	0.01	0.30				
					35966	1	485.00	486.00	1.00	0.05	0.10				
					35967	1	486.00	487.00	1.00	0.10	0.20				
					35968	1	487.00	488.00	1.00	0.10	0.10				
					35969	1	488.00	489.00	1.00	0.02	0.10				
					35970	1	489.00	490.00	1.00	0.01	0.20				
490.60	501.40	Diorite	DIO	Diorite Dike: dark green, fine grained, massive uniform sharp contact at 50 CA; possible hornblende lamprophyre	35971	1	490.00	490.60	0.60	0.01	0.10				
					35972	1	490.60	491.00	0.40	0.04	0.10				
					35973	1	491.00	492.00	1.00	0.01	0.10				
					35976	1	492.00	493.00	1.00	0.01	0.10				
				493.00 - 498 scattered quartz veins at 40 CA	35977	1	493.00	494.00	1.00	0.01	0.20				
					35978	1	494.00	495.00	1.00	0.01	0.70				
					35979	1	495.00	496.00	1.00	0.01	0.10				
					35980	1	496.00	497.00	1.00	0.01	0.10				
					35981	1	497.00	498.00	1.00	0.01	0.30				
					35982	1	498.00	499.00	1.00	0.01	0.10				
					35983	1	499.00	500.00	1.00	0.01	0.10				
					35984	1	500.00	501.00	1.00	0.01	0.10				
					35986	1	501.00	501.40	0.40	0.01	0.40				
501.40	507.10	CGL	CGL	Hematized Conglomerate:	35987	1	501.40	502.00	0.60	0.01	0.10				
					35988	1	502.00	503.00	1.00	0.01	0.10				
					35989	1	503.00	504.00	1.00	0.02	0.10				
					35990	1	504.00	505.00	1.00	0.01	0.10				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					35991	1	505.00	506.00	1.00	0.02	0.10				
					35992	1	506.00	507.10	1.10	0.01	0.10				
507.10	510.60	GABBRO	GB	dark green massive uniform; 60% mafic; sharp contact at 70-80 CA	35993	1	507.10	508.00	0.90	0.01	0.10				
					35996	1	508.00	509.00	1.00	0.01	0.10				
					35997	1	509.00	510.00	1.00	0.01	0.10				
				510.60 - 511.40 hematitic conglomerate	35998	1	510.00	510.60	0.60	0.06	0.10				
					35999	1	510.60	511.00	0.40	0.06	0.10				
510.60	540.20	CGL	CGL	as above:	36000	1	511.00	512.00	1.00	0.03	0.10				
				513.60 - 518.00 hematitic	36001	1	512.00	513.00	1.00	0.01	0.10				
				513.20 - 5 cm quartz vein at 40 CA	36002	1	513.00	514.00	1.00	0.01	0.10				
					36003	1	514.00	515.00	1.00	0.01	0.10				
				515.60 - 515.95 gabbro, contact at 70 CA	36004	1	515.00	516.00	1.00	0.01	0.10				
					36006	1	516.00	517.00	1.00	0.01	0.10				
					36007	1	517.00	518.00	1.00	0.01	0.10				
					36008	1	518.00	519.00	1.00	0.01	0.10				
					36009	1	519.00	520.00	1.00	0.01	0.10				
					36010	1	520.00	521.00	1.00	0.01	0.10				
					36011	1	521.00	522.00	1.00	0.03	0.10				
				522.15 - 3 cm quartz vein at 10 CA	36012	1	522.00	523.00	1.00	0.03	0.10				
					36013	1	523.00	524.00	1.00	0.01	0.10				
					36016	1	524.00	525.00	1.00	0.01	0.10				
					36017	1	525.00	526.00	1.00	0.01	0.10				
					36018	1	526.00	527.00	1.00	0.03	0.10				
					36019	1	527.00	528.00	1.00	0.01	0.10				
					36020	1	528.00	529.00	1.00	0.06	0.10				
					36021	1	529.00	530.00	1.00	0.01	0.10				
					36022	1	530.00	531.00	1.00	0.01	0.10				
					36023	1	531.00	532.00	1.00	0.01	0.10				
					36024	1	532.00	533.00	1.00	0.01	0.10				
					36026	1	533.00	534.00	1.00	0.01	0.10				
					36027	2	534.00	535.00	1.00	0.01	0.10				
					36028	2	535.00	536.00	1.00	0.01	0.10				
					36029	2	536.00	537.00	1.00	0.01	0.10				
					36030	2	537.00	538.00	1.00	0.01	0.80				
				538.00 - 540.20 hematized	36031	2	538.00	539.00	1.00	0.01	0.40				
					36032	3	539.00	540.20	1.20	0.01	0.40				
540.20	541.30	LAM	LAM	Lamprophyre: as above: hornblende phenocrysts <2mm	36033	1	540.20	541.30	1.10	0.01	0.20				
					36036	1	541.30	542.00	0.70	0.01	0.20				
541.30	548.90	CGL	CGL	as above: contact at 70 CA	36037	1	542.00	543.00	1.00	0.14	0.20				
					36038	1	543.00	544.00	1.00	0.01	0.30				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
				541.3 - 545.00 hematized	36039	1	544.00	545.00	1.00	0.03	0.40				
					36040	1	545.00	546.00	1.00	0.01	0.30				
					36041	1	546.00	547.00	1.00	0.07	0.50				
					36042	1	547.00	548.00	1.00	0.02	0.10				
548.90	575.46	SYN	SYN	Porphyritic Syenite: pinkish green, fine grained,	36043	1	548.00	548.90	0.90	0.01	0.10				
				porphyritic, fine grained, 1mm, massive, uniform, sharp	36044	1	548.90	550.00	1.10	0.01	0.10				
				contact at 60 CA; minor quartz carbonate veining at 40	36046	1	550.00	551.00	1.00	0.03	0.10				
				CA; traces chalcopyrite.	36047	1	551.00	552.00	1.00	0.02	0.10				
					36048	1	552.00	553.00	1.00	0.01	0.10				
					36049	1	553.00	554.00	1.00	0.02	0.10				
					36050	1	554.00	555.00	1.00	0.03	0.10				
				555.10 - trace of chalcopyrite	36051	1	555.00	556.00	1.00	0.01	0.10				
					36052	1	556.00	557.00	1.00	0.01	0.10				
				557.85 - 1 cm quartz vein at 30 CA	36053	1	557.00	558.00	1.00	0.01	0.20				
					36056	1	558.00	559.00	1.00	0.01	0.20				
				558.90 - 1 cm quartz vein at 40 CA with epidote	36057	1	559.00	560.00	1.00	0.01	0.10				
					36058	1	560.00	561.00	1.00	0.01	0.10				
				560.35 - 1 cm quartz vein at 40 CA with epidote	36059	1	561.00	562.00	1.00	0.01	0.10				
					36060	1	562.00	563.00	1.00	0.01	0.10				
					36061	1	563.00	564.00	1.00	0.01	0.20				
					36062	1	564.00	565.00	1.00	0.01	0.10				
					36063	1	565.00	566.00	1.00	0.01	0.20				
				566.00 - 1 cm quartz vein at 40 CA	36064	1	566.00	567.00	1.00	0.01	0.20				
					36066	1	567.00	568.00	1.00	0.01	0.20				
					36067	1	568.00	569.00	1.00	0.01	0.10				
					36068	1	569.00	570.00	1.00	0.01	0.10				
					36069	1	570.00	571.00	1.00	0.03	0.20				
					36070	1	571.00	572.00	1.00	0.01	0.20				
					36071	1	572.00	573.00	1.00	0.01	0.10				
					36072	1	573.00	574.00	1.00	0.01	0.10				
					36073	1	574.00	575.00	1.00	0.01	0.20				
				574.40 - 575.46 strongly hematized	36076	1	575.00	575.46	0.46	0.01	0.20				
					36077	1	575.46	576.00	0.54	0.01	0.20				
575.46	576.76	DIABASE	DIA	dark grey, fine grained massive uniform, ophitic	36078	1	576.00	576.76	0.76	0.01	0.10				
				texture; sharp contact at 80 CA.	36079	1	576.76	578.00	1.24	0.01	0.30				
576.76	578.30	SYN	SYN	as above:	36080	1	578.00	579.06	1.06	0.02	0.30				
					36081	1	579.06	580.00	0.94	0.01	0.20				
578.30	579.06	Fault Zone	FZ	strongly sheared at 70 CA;	36082	1	580.00	581.00	1.00	0.01	0.10				
				578.3 - 578.70 pink quartz carbonate veining at 50 CA	36083	1	581.00	582.00	1.00	0.01	0.30				
					36084	1	582.00	583.00	1.00	0.01	0.10				
579.06	600.00	SYENITE	SYN	as above	36086	1	583.00	584.00	1.00	0.01	0.20				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					36087	1	584.00	585.00	1.00	0.01	0.10				
					36088	1	585.00	586.00	1.00	0.02	0.30				
					36089	1	586.00	587.00	1.00	0.02	0.20				
					36090	1	587.00	588.00	1.00	0.05	0.10				
					36091	1	588.00	589.00	1.00	0.04	0.10				
					36092	1	589.00	590.00	1.00	0.01	0.10				
					36093	1	590.00	591.00	1.00	0.05	0.10				
					36096	1	591.00	592.00	1.00	0.01	0.10				
					36097	1	592.00	593.00	1.00	0.01	0.10				
					36098	1	593.00	594.00	1.00	0.01	0.20				
				593.98 - 594.5 Diorite Dike: contact at 30 and 80 CA	36099	1	594.00	595.00	1.00	0.01	0.10				
					36100	1	595.00	596.00	1.00	0.01	0.20				
					36101	1	596.00	597.00	1.00	0.01	0.10				
					36102	1	597.00	598.00	1.00	0.01	0.10				
					36103	1	598.00	599.00	1.00	0.01	0.10				
					36104	1	599.00	600.00	1.00	0.01	0.10				
				DDH core stored at Matachewan											
				EOH											
Downhole Tests:															
	Depth	AZ	DIP												
	54	334.4	-59.7												
	108	335.6	-59.6												
	153	343.2	-58.7												
	204	340.3	-57.1												
	252	347.2	-57.5												
	303	346.7	-55.2												
	351	346..5	-54.1												
	405	351	-51.6												
	453	342.6	-50.1												
	504	354.6	-48.3												
	555	352.2	-45.3												
	600	354.3	-44.6												

Opawica Explorations Inc.

Matachewan
 DDH#: OPW-07-005
 Az and Dip: 330/-65
 E.O.H: 201 m

GRID LOCATION: Powell Twp., Ontario
 GRID: OPW: 4E 13+50S
 UTM, type: 0522799E, 5311863N: Nad: 83 Zone: 17
 Elev.:

Claim: 511486
 Drill Company: Downing: NQ Core
 Start: July 15, 2007; End: July 17, 2007
 Logged by: Fred Sharpley

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
0.00	2.87		OVB												
2.87	82.90	Greywacke	GWE	medium grey, fine grained, fairly massive	36105		2.87	4.00	1.13	0.01	0.10				
					36106		4.00	5.00	1.00	0.01	0.10				
				6.20 10 cm quartz vein at 50 CA	36107		5.00	6.00	1.00	0.01	0.10				
				7.10 2 cm quartz vein at 30 CA	36108		6.00	7.00	1.00	0.01	0.10				
				7.40 8 cm quartz vein at 50 CA	36109		7.00	8.00	1.00	0.01	0.10				
					36110		19.00	20.00	1.00	0.01	0.10				
				19.20 10 cm quartz vein at 70 CA	36111		20.00	21.00	1.00	0.01	0.10				
					36112		21.00	22.00	1.00	0.01	0.10				
				25.95 4 cm quartz vein at 50 CA	36113		22.00	23.00	1.00	0.01	0.10				
				26.60 4 cm quartz vein at 70 CA	36115		23.00	24.00	1.00	0.01	0.20				
					36116		24.00	25.00	1.00	0.01	0.10				
				12.50 - 20.00 autobrecciated, 2-3% disseminated pyrite	36117		25.00	26.00	1.00	0.01	0.20				
					36118		26.00	27.00	1.00	0.01	0.10				
					36119		27.00	28.00	1.00	0.01	0.10				
				41.00 - 10 cm quartz vein at 60 CA	36120		40.00	41.00	1.00	0.01	0.20				
				50.3 3 cm quartz vein at 70 CA	36121		41.00	42.00	1.00	0.01	0.10				
					36122	2	58.00	59.00	1.00	0.03	0.20				
				58.00 - 82.90 1-3% disseminated pyrite; weak sericite alteration	36123	2	59.00	60.00	1.00	0.02	0.20				
					36124	2	60.00	61.00	1.00	0.01	0.10				
					36127	2	61.00	62.00	1.00	0.02	0.10				
					36128	2	62.00	63.00	1.00	0.01	0.20				
					36129	2	63.00	64.00	1.00	0.01	0.10				
					36130	2	64.00	65.00	1.00	0.01	0.20				
					36131	2	65.00	66.00	1.00	0.01	0.20				
					36132	2	66.00	67.00	1.00	0.01	0.30				
					36133	2	67.00	68.00	1.00	0.01	0.40				
					36135		68.00	69.00	1.00	0.01	0.40				
					36136	2	69.00	70.00	1.00	0.01	0.70				
					36137	2	70.00	71.00	1.00	0.01	0.30				
					36138	2	71.00	72.00	1.00	0.01	0.10				
					36139	2	72.00	73.00	1.00	0.01	0.10				
					36140	2	73.00	74.00	1.00	0.01	0.20				
					36141	2	74.00	75.00	1.00	0.01	0.10				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					36142	2	75.00	76.00	1.00	0.01	0.10				
					36145	2	76.00	77.00	1.00	0.02	0.10				
					36146	2	77.00	78.00	1.00	0.01	0.10				
					36147	2	78.00	79.00	1.00	0.01	0.20				
					36148	2	79.00	80.00	1.00	0.01	0.40				
					36149	2	80.00	81.00	1.00	0.01	0.10				
					36150	2	81.00	82.00	1.00	0.01	0.10				
					36151	2	82.00	83.00	1.00	0.01	0.20				
82.90	114.55	Greywacke	GWE	fine grained, medium grey, massive, uniform; sharp contact at 10 CA; possibly greywacke	36152		83.00	84.00	1.00	0.01	0.20				
					36153		84.00	85.00	1.00	0.04	0.20				
					36155		85.00	86.00	1.00	0.01	0.10				
					36156		86.00	87.00	1.00	0.01	0.10				
					36157		87.00	88.00	1.00	0.02	0.20				
					36158		88.00	89.00	1.00	0.01	0.10				
					36159		89.00	90.00	1.00	0.01	0.10				
					36160		90.00	91.00	1.00	0.01	0.10				
					36161		91.00	92.00	1.00	0.01	0.30				
					36162		92.00	93.00	1.00	0.01	0.20				
					36165	8	93.00	94.00	1.00	0.03	0.20				
				93.10 - 95.50 5-10% finely disseminated pyrite in chloritized zone	36166	8	94.00	95.00	1.00	0.01	0.20				
					36167	8	95.00	96.00	1.00	0.01	0.20				
					36168		96.00	97.00	1.00	0.01	0.20				
					36169		97.00	98.00	1.00	0.01	0.10				
					36170		98.00	99.00	1.00	0.01	0.10				
					36171		99.00	100.00	1.00	0.01	0.10				
					36172		100.00	101.00	1.00	0.01	0.10				
					36173		101.00	102.00	1.00	0.02	0.10				
				113.7 - 10 cm quartz vein at 50 CA	36175		102.00	103.00	1.00	0.03	0.10				
114.55	116.30	DIORITE	DIO	light greenish, medium grained, massive uniform; sharp contact at 50 CA	36176		113.00	114.00	1.00	0.01	0.50				
					36177		121.00	122.00	1.00	0.01	0.30				
					36178		134.00	135.00	1.00	0.01	0.30				
116.30	174.30	Greywacke	GWE	as above:	36179		135.00	136.00	1.00	0.01	0.30				
					36180		136.00	137.00	1.00	0.01	0.10				
					36181	2	165.00	166.00	1.00	0.21	1.50				
				121.25 - 10 cm quartz vein at 50 CA	36182	2	166.00	167.00	1.00	0.01	0.20				
					36183	1	193.00	194.00	1.00	0.01	0.20				
					36184	1	194.00	195.00	1.00	0.04	0.10				
				134.20 - 7 cm quartz vein at 60 CA	36185	1	195.00	196.00	1.00	0.01	0.10				
					36186	1	196.00	197.00	1.00	0.01	0.10				
				135.7 8 cm quartz vein at 50 CA											
				136.1 2 cm quartz vein at 40 CA											

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
				165.00 - 167.00 weak sericite alteration; 1-2% pyrite											
174.30	175.54	Diorite	DIO	Diorite Dike: as above: contact at 20 CA											
175.54	182.60	Greywacke	GWE	as above											
182.60	184.50	Diabase	DIA	black, very fine grained, sharp contact at 20 CA											
184.50	201.00	Greywacke	GWE	as above:											
				194.90 - 196.00 20% quartz veining at 40 CA; minor chalcopyrite											
				EOH											
				core stored at Matachewan											
Downhole Tests:															
	Depth	AZ	DIP												
	105	327.5	-66.5												
	150	332.7	-65.7												
	201	336.2	-66.2												

Opawica Explorations Inc.

Matachewan
 DDH#: OPW-07-006
 Az and Dip: 155/-65
 E.O.H: 432.4 m

GRID LOCATION: Powell Twp., Ontario
 GRID: OPW: 534W 0+00S
 UTM, type: 0521329E, 5312566N: Nad: 83 Zone: 17
 Elev.:

Claim: L372910
 Drill Company: Downing: NQ Core
 Start: July 17, 2007; End: July 19, 2007
 Logged by: Fred Sharpley

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
0.00	1.40		OVB												
1.40	26.75	Diabase	DIA	dark grey, fine grained to medium grained, massive uniform, ophitic texture	36498	5	140.80	142.00	1.20	0.01	0.20				
					36499	5	142.00	143.00	1.00	0.01	0.10				
					36500	5	143.00	144.00	1.00	0.12	0.10				
26.75	34.10	Greywacke	GWE	as above: sharp contact at 70 CA; chilled contact; medium grey, very fine grained, massive	36501	5	144.00	145.00	1.00	0.10	0.10				
					36502	5	145.00	146.00	1.00	0.11	0.10				
					36503	4	146.00	147.00	1.00	0.08	0.20				
				33.1-33.3 diabase	36504	4	147.00	148.00	1.00	0.11	0.40				
					36505	4	148.00	149.00	1.00	0.54	1.10				
34.10	140.80	Diabase	DIA	as above: sharp contact at 20 CA	36507	4	149.00	150.00	1.00	0.08	0.10				
					36508	4	150.00	151.00	1.00	0.01	0.10				
				55.5-56.0 Mafic Dike: dark grey, massive, uniform sharp contact at 30 CA	36509	4	151.00	152.00	1.00	0.01	0.10				
					36510	4	152.00	153.00	1.00	0.01	0.10				
					36511	4	153.00	154.00	1.00	0.01	0.10				
140.80	157.00	Greywacke	GWE	as above: light to medium grey, bleached, moderate to strongly silicified, 3-5% finely disseminated pyrite	36512	4	154.00	155.00	1.00	0.01	0.10				
				Sharp contact at 60 CA	36513	4	155.00	156.00	1.00	0.01	0.10				
					36514	4	156.00	157.00	1.00	0.02	0.10				
					36517	3	157.00	158.00	1.00	0.01	0.10				
				140.8-146.0 hematite alteration; 5% very fine disseminated pyritepyrite	36518	3	158.00	159.00	1.00	0.01	0.10				
					36519	3	159.00	160.00	1.00	0.01	0.10				
					36520	3	160.00	161.00	1.00	0.01	0.10				
157.00	158.00	Mafic	MAF	Mafic Dike: dark green, massive uniform, sharp contact at 20 and 70 CA	36521	3	161.00	162.00	1.00	0.02	0.10				
					36522	3	162.00	163.00	1.00	0.01	0.10				
					36523	3	163.00	164.00	1.00	0.01	0.10				
158.00	186.50	Greywacke	GWE	as above: 140.8-157.0	36524	3	164.00	165.00	1.00	0.01	0.10				
				158.0-161.2 white feldspar phenocrysts; poss. FP	36525	3	165.00	166.00	1.00	0.01	0.10				
				143.4 1cm quartz vein at 50 CA	36527	3	166.00	167.00	1.00	0.01	0.10				
					36528	3	167.00	168.00	1.00	0.01	0.20				
				149.2 5cm quartz vein at 40 CA	36529	3	168.00	169.00	1.00	0.17	0.30				
					36530	3	169.00	170.00	1.00	0.19	0.40				
					36531	3	170.00	171.00	1.00	0.01	0.20				
					36532	3	171.00	172.00	1.00	0.01	0.10				
					36533	3	172.00	173.00	1.00	0.02	0.30				
					36534	3	173.00	174.00	1.00	0.03	0.70				
					36537	3	174.00	175.00	1.00	0.18	1.30				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					36538	3	175.00	176.00	1.00	0.05	1.20				
				176.36- 179.30 40% quartz veining at 50 CA; 1-3% disseminated pyrite, fine grained.	36539	3	176.00	177.00	1.00	0.01	1.50				
					36540	3	177.00	178.00	1.00	0.16	1.30				
					36541	3	178.00	179.00	1.00	0.62	4.00				
					36542	2	179.00	180.00	1.00	0.01	0.50				
					36543	2	180.00	181.00	1.00	0.18	0.60				
					36544	2	181.00	182.00	1.00	0.09	0.40				
					36545	2	182.00	183.00	1.00	0.10	0.10				
					36547	2	183.00	184.00	1.00	0.12	0.40				
					36548	2	184.00	185.00	1.00	0.01	0.10				
					36549	2	185.00	186.00	1.00	0.01	0.10				
186.50	303.40	Diabase	DIA	as above: contact at 20 CA	36550	2	186.00	186.50	0.50	0.01	0.20				
					36551	3	382.00	382.90	0.90	0.01	0.10	0.018			
				206.2-206.9 Mafic Dike: medium grey, very fine grained massive uniform, sharp contact at 20 CA	36552	3	382.90	384.00	1.10	0.08	0.10	0.001			
					36553	3	384.00	385.00	1.00	0.11	0.20	0.001			
					36554	3	385.00	386.00	1.00	0.26	0.10	0.001			
				273.3-274.8 Mafic Dike: as above:	36557	3	386.00	387.00	1.00	0.05	0.10	0.001			
					36558	3	387.00	388.00	1.00	0.03	0.10	0.001			
303.30	312.65	Mafic Dike	MAF	as above: contact at 20 CA	36559	3	388.00	389.00	1.00	0.01	0.10	0.001			
					36560	3	389.00	390.00	1.00	0.01	0.10	0.001			
312.65	382.90	Diabase	DIA	as above:	36561		390.00	391.00	1.00	0.01	0.10				
					36562		391.00	392.00	1.00	0.01	0.20				
382.90	390.10	SYENITE	SYN	pale pink, fine grained, massive uniform; sharp contact at 20 CA; pale green alteration, chlorite	36563		392.00	393.00	1.00	0.01	0.10				
					36564		393.00	394.00	1.00	0.01	0.10				
					36565		394.00	395.00	1.00	0.01	0.10				
					36567		395.00	396.00	1.00	0.01	0.10				
390.10	396.60	Diabase	DIA	as above: contact at 20 CA	36568		396.00	396.60	0.60	0.01	0.10				
					36569	3	396.60	397.00	0.40	0.01	0.30	0.007			
					36570	3	397.00	398.00	1.00	0.02	0.40	0.071			
					36571	3	398.00	399.10	1.10	0.01	0.10	0.001			
					36572	1	399.10	400.00	0.90	0.01	0.10				
					36573	1	400.00	401.00	1.00	0.01	0.10				
					36574	1	401.00	402.00	1.00	0.02	0.10				
					36577	1	402.00	403.00	1.00	0.02	0.10				
396.60	399.10	Syenite	SYN	as above: contact at 20 CA and 60 CA; 1-3% fine disseminated pyrite	36578	1	403.00	404.00	1.00	0.03	0.10				
					36579	1	404.00	405.00	1.00	0.01	0.10				
					36580	1	405.00	406.00	1.00	0.02	0.10				
399.10	416.30	Mafic Dike	MAF	medium grey-black, moderately sheared at 40-50 CA 1-3% disseminated pyrite; numerous quartz carbonate veining at 40 CA; hornblende and white feldspar phenocrysts; 1-2% pyrite.	36581	1	406.00	407.00	1.00	0.02	0.10				
					36582	1	407.00	408.00	1.00	0.01	0.10				
					36583	1	408.00	409.00	1.00	0.01	0.10				
					36584	1	409.00	410.00	1.00	0.14	0.10				
					36585	1	410.00	411.00	1.00	0.01	0.10				

Opawica Explorations Inc.

Matachewan
 DDH#: OPW-07-007
 Az and Dip: 330/-50
 E.O.H: 201 m

GRID LOCATION: Powell Twp., Ontario
 GRID: OPW: 2E 15+40S
 UTM, type: 0522717E, 5311594N: Nad: 83 Zone: 17
 Elev.:

Claim: MR37455
 Drill Company: Downing: NQ Core
 Start: July 19, 2007; End: July 21, 2007
 Logged by: Fred Sharpley

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
0.00	4.60		OVB												
4.60	9.10	Diabase	DIA	dark grey, fine grained, fairly massive; contact at 60 CA	36187	2	9.00	10.00	1.00	0.01	0.20				
					36188	1	10.00	11.00	1.00	0.01	0.40				
9.10	27.60	Greywacke:	GWE	medium grey, very fine grained, massive	36191	2	57.00	58.10	1.10	0.01	0.70				
					36192	2	58.10	58.85	0.75	0.01	0.30				
				9.10 - 10.26 Conglomerate: 1-2% pyrite	36193	1	58.85	60.00	1.15	0.01	0.40				
					36195	1	60.00	61.00	1.00	0.01	0.40				
27.60	58.10	Diabase	DIA	as above: medium grained, ophitic texture	36196	1	61.00	62.00	1.00	0.01	0.30				
					36197	1	62.00	63.00	1.00	0.01	0.20				
58.10	63.83	Greywacke	GWE	as above:	36198	1	63.00	63.83	0.83	0.01	0.20				
					36199	5	63.83	65.00	1.17	0.01	0.20	0.02			
				58.10 - 58.85 Conglomerate	36200	5	65.00	66.00	1.00	0.02	0.20	0.01			
					36201	5	66.00	67.00	1.00	0.01	0.20	0.01			
					36202	5	67.00	68.00	1.00	0.01	0.50	0.01			
					36205	4	68.00	69.00	1.00	0.01	0.10	0.01			
					36206	4	69.00	70.00	1.00	0.01	0.20	0.01			
					36207	4	70.00	71.00	1.00	0.01	0.10	0.01			
63.85	84.10	Greywacke	GWE	Alteration Zone: moderate to strong quartz sericite; 3-5% disseminated fine pyrite; green carbonate fragments; foliated at 50 CA; brecciated, silicified	36208	4	71.00	72.00	1.00	0.03	0.20	0.01			
					36209	4	72.00	73.00	1.00	0.01	0.10	0.01			
					36210	4	73.00	74.00	1.00	0.02	0.20	0.009			
					36211	4	74.00	75.00	1.00	0.01	0.10	0.009			
					36212	5	75.00	76.00	1.00	0.01	0.10	0.006			
					36213	5	76.00	77.00	1.00	0.01	0.20	0.006			
					36215	6	77.00	78.00	1.00	0.01	0.20	0.008			
					36216	6	78.00	79.00	1.00	0.01	0.10	0.005			
					36217	6	79.00	80.00	1.00	0.01	0.20	0.009			
					36218	6	80.00	81.00	1.00	0.01	0.10	0.011			
					36219	6	81.00	82.00	1.00	0.01	0.10	0.015			
					36220	6	82.00	83.00	1.00	0.01	0.20	0.012			
					36221	6	83.00	84.10	1.10	0.01	0.10	0.011			
					36222		84.10	85.00	0.90	0.01	0.20	0.022			
					36225		85.00	85.94	0.94	0.01	0.30	0.039			
					36226	4	85.94	87.00	1.06	0.02	0.10	0.007			
					36227	4	87.00	88.00	1.00	0.02	0.30	0.003			
					36228	4	88.00	89.00	1.00	0.01	0.10	0.002			

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					36229	4	89.00	90.00	1.00	0.01	0.10	0.008			
					36230	4	90.00	91.00	1.00	0.01	0.10	0.005			
					36231	4	91.00	92.00	1.00	0.02	0.10	0.009			
					36232	4	92.00	93.00	1.00	0.01	0.10	0.008			
					36233	4	93.00	94.00	1.00	0.02	0.10	0.004			
84.10	85.94	Mafic Dike	MAF	dark green, massive uniform, leucoxene specks; sharp contact at 50 CA	36235	4	94.00	95.00	1.00	0.01	0.20	0.005			
					36236	4	95.00	96.00	1.00	0.01	0.30	0.003			
					36237	4	96.00	97.00	1.00	0.01	0.50	0.006			
					36238	4	97.00	98.00	1.00	0.01	0.20	0.003			
85.94	103.66	Greywacke	GWE	Alteration Zone: moderate to strong quartz sericite; as above: yellow sericite	36239	4	98.00	99.00	1.00	0.02	0.20	0.004			
					36240	4	99.00	100.00	1.00	0.02	0.40	0.004			
					36241	4	100.00	101.00	1.00	0.01	0.30	0.004			
					36242	4	101.00	102.00	1.00	0.01	0.40	0.006			
					36245	4	102.00	103.00	1.00	0.01	0.40	0.004			
					36246	4	103.00	103.66	0.66	0.01	0.10	0.004			
					36247	2	103.66	104.00	0.34	0.10	0.20				
					36248	2	104.00	105.00	1.00	0.03	0.10				
					36249	2	105.00	106.00	1.00	0.01	0.10				
					36250	1	106.00	107.00	1.00	0.01	0.10				
					36251	1	107.00	108.00	1.00	0.01	0.10				
					36252	1	108.00	109.00	1.00	0.10	0.10				
					36253	1	109.00	110.00	1.00	0.01	0.10				
					36255	1	110.00	111.00	1.00	0.08	0.10				
					36256	1	111.00	112.00	1.00	0.01	0.10				
					36257	1	112.00	113.00	1.00	0.01	0.10				
					36258	1	113.00	114.00	1.00	0.01	0.10				
					36259	1	114.00	115.00	1.00	0.01	0.10				
					36260	1	115.00	116.00	1.00	0.01	0.10				
					36261	1	116.00	117.00	1.00	0.01	0.10				
103.66	104.00	Fault Zone	FZ	strongly sheared at 50 CA; chloritized	36262	1	117.00	118.00	1.00	0.01	0.10				
104.00	118.10	Greywacke	GWE	as above: 1-2% pyrite	36263	10	118.00	119.00	1.00	0.04	0.40				
					36266	1	119.00	120.00	1.00	0.01	0.10				
					36267	1	120.00	121.00	1.00	0.01	0.10				
					36268	1	121.00	122.00	1.00	0.01	0.10				
					36269	1	122.00	123.00	1.00	0.01	0.10				
					36270	1	123.00	124.00	1.00	0.01	0.10				
					36271	1	124.00	125.00	1.00	0.01	0.10				
					36272	1	125.00	126.00	1.00	0.01	0.10				
					36273	1	126.00	127.00	1.00	0.01	0.10				
					36274	1	127.00	128.00	1.00	0.01	0.10				
					36276	1	128.00	129.00	1.00	0.01	0.10				
					36277	1	129.00	130.00	1.00	0.01	0.20				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					36278	1	130.00	131.00	1.00	0.01	0.10				
					36279	1	131.00	132.00	1.00	0.01	0.10				
					36280	1	132.00	133.00	1.00	0.01	0.10				
					36281	1	133.00	134.00	1.00	0.01	0.20				
118.10	119.00	Mafic Dike	MAF	dark green, massive uniform, leucoxene specks;	36282	1	134.00	135.00	1.00	0.01	0.10				
				contact at 20 and 50 CA; 5-10% fine to medium pyrite	36283	1	135.00	136.00	1.00	0.01	0.30				
119.00	201.00	Siltstone	SILT	light grey, very fine grained, banded at 40 CA; 1-2%	36286	1	136.00	137.00	1.00	0.01	0.10				
				disseminated pyrite	36287	1	137.00	138.00	1.00	0.01	0.20				
					36288	1	138.00	139.00	1.00	0.02	0.30				
				119.00 - 133.10 weakly bleached	36289	1	139.00	140.00	1.00	0.02	0.10				
					36290	1	140.00	141.00	1.00	0.01	0.10				
					36291	1	141.00	142.00	1.00	0.01	0.10				
					36292	1	142.00	143.00	1.00	0.02	0.10				
					36293	1	143.00	144.00	1.00	0.01	0.10				
					36294	1	144.00	145.00	1.00	0.01	0.10				
					36296	1	145.00	146.00	1.00	0.01	0.20				
					36297	1	146.00	147.00	1.00	0.01	0.10				
					36298	1	147.00	148.00	1.00	0.01	0.10				
					36299	1	148.00	149.00	1.00	0.01	0.20				
					36300	1	149.00	150.00	1.00	0.01	0.30				
					36301	1	150.00	151.00	1.00	0.04	0.10				
					36302	1	151.00	152.00	1.00	0.01	0.10				
					36303	1	152.00	153.00	1.00	0.01	0.10				
					36306	1	153.00	154.00	1.00	0.01	0.50				
					36307	1	154.00	155.00	1.00	0.03	1.20				
					36308	1	155.00	156.00	1.00	0.01	0.40				
					36309	1	156.00	157.00	1.00	0.01	0.20				
					36310	1	157.00	158.00	1.00	0.01	0.40				
					36311	1	158.00	159.00	1.00	0.01	0.30				
					36312	1	159.00	160.00	1.00	0.01	0.20				
					36313	1	160.00	161.00	1.00	0.01	0.20				
					36314	1	161.00	162.00	1.00	0.01	0.10				
					36316	1	162.00	163.00	1.00	0.01	0.20				
					36317	1	163.00	164.00	1.00	0.01	0.10				
					36318	1	164.00	165.00	1.00	0.01	0.20				
					36319	1	165.00	166.00	1.00	0.01	0.10				
					36320	1	166.00	167.00	1.00	0.01	0.90				
					36321	1	167.00	168.00	1.00	0.01	0.10				
					36322	1	168.00	169.00	1.00	0.02	0.10				
					36323	1	169.00	170.00	1.00	0.01	0.10				
					36326	5	170.00	171.00	1.00	0.01	1.60				
					36327	5	171.00	172.00	1.00	0.02	1.80				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					36328	5	172.00	173.00	1.00	0.18	6.90				
					36329	5	173.00	174.00	1.00	2.38	8.50				
					36330	1	174.00	175.00	1.00	3.10	2.10				
					36331	1	175.00	176.00	1.00	0.01	0.40				
					36332	1	176.00	177.00	1.00	0.01	0.10				
					36333	1	177.00	178.00	1.00	0.24	1.10				
					36334	1	178.00	179.00	1.00	0.01	0.10				
				170.4 - 173.50 strongly chloritized, 3-5% disseminated pyrite											
					36336	1	179.00	180.00	1.00	0.01	0.10				
					36337	1	180.00	181.00	1.00	0.01	0.10				
					36338	1	181.00	182.00	1.00	0.03	0.10				
					36339	1	182.00	183.00	1.00	0.02	0.30				
					36340	1	183.00	184.00	1.00	0.01	0.30				
				175.60 - 176.30 Argillite; black color, very fine grained contact at 20 CA											
					36341	1	184.00	185.00	1.00	0.01	1.00				
					36342	1	185.00	186.00	1.00	0.01	0.10				
					36343	1	186.00	187.00	1.00	0.02	0.10				
					36346	1	187.00	188.00	1.00	0.01	0.10				
					36347	1	188.00	189.00	1.00	0.01	0.10				
					36348	5	189.00	190.00	1.00	0.02	0.50				
					36349	5	190.00	191.00	1.00	0.03	1.20				
					36350	5	191.00	192.00	1.00	0.03	1.30				
					36351	5	192.00	193.00	1.00	0.01	1.10				
					36352	1	193.00	194.00	1.00	0.01	0.20				
					36353	1	194.00	195.00	1.00	0.01	0.10				
					36354	1	195.00	196.00	1.00	0.02	0.20				
					36356	1	196.00	197.00	1.00	0.05	1.40				
				189.00 - 197.00 moderately chloritized, 3-5% disseminated pyrite											
					36357	1	197.00	198.00	1.00	0.01	0.30				
					36358	1	198.00	199.00	1.00	0.14	0.30				
					36359	1	199.00	200.00	1.00	0.04	0.30				
					36360	1	200.00	201.00	1.00	0.05	0.20				
				EOH											
				core stored at Matachewan											
Downhole Tests:															
	Depth	AZ	DIP												
	54	323.1 ?	-51.6												
	105	333.7	-50.3												
	153	338.6	-49.9												
	201	338.2	-49.9												

Opawica Explorations Inc.

Matachewan
DDH#: OPW-07-008
Az and Dip: 330/-50
E.O.H: 201 m

GRID LOCATION: Powell Twp., Ontario
GRID: OPW: 2E 13+40S
UTM, type: 0522625E, 5311771N: Nad: 83 Zone: 17
Elev.:

Claim: MR37456, L372903, 511486
Drill Company: Downing: NQ Core
Start: July 20, 2007; End: July 21, 2007
Logged by: Fred Sharpley

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
0.00	2.50		OVB												
2.50	16.90	Greywacke	GWE	medium grey, very fine grained, weakly banded at 30 CA; 1-3% disseminated pyrite	36361	2	2.50	3.00	0.50	0.01	0.10				
					36362	2	3.00	4.00	1.00	0.01	0.10				
					36363	2	4.00	5.00	1.00	0.02	0.10				
					36364	2	5.00	6.00	1.00	0.02	0.10				
					36365	2	6.00	7.00	1.00	0.01	0.10				
					36366	2	7.00	8.00	1.00	0.01	0.20				
					36367	2	8.00	9.00	1.00	0.01	0.10				
					36368	2	9.00	10.00	1.00	0.01	0.10				
					36369	2	10.00	11.00	1.00	0.01	0.20				
					36371	2	11.00	12.00	1.00	0.01	0.10				
					36372	2	12.00	13.00	1.00	0.01	0.10				
					36373	2	13.00	14.00	1.00	0.01	0.10				
					36374	2	14.00	15.00	1.00	0.01	0.10				
					36375	2	15.00	16.00	1.00	0.01	0.10				
					36376	2	16.00	16.90	0.90	0.01	0.20				
					36377	2	29.00	30.00	1.00	0.01	0.10				
16.90	29.05	Diabase	DIA	dark grey, medium grained, massive uniform, ophitic texture, chilled contact at 50 CA	36378	2	30.00	31.00	1.00	0.01	0.20				
					36381	2	31.00	32.00	1.00	0.01	0.10				
					36382	2	32.00	33.00	1.00	0.01	0.20				
29.05	37.30	FP	FP	Feldspar Porphyry: medium grey groundmass, fine grained, in coarse grained phenocrysts, 4 mm, white feldspar; 1% disseminated pyrite; contact at 50 CA	36383	2	33.00	34.00	1.00	0.01	0.20				
					36384	2	34.00	35.00	1.00	0.01	0.10				
					36385	2	35.00	36.00	1.00	0.01	0.10				
					36386	2	36.00	37.30	1.30	0.01	0.10				
				30.0-32.0 30% quartz veining at low angles	36387	2	37.30	38.00	0.70	0.01	0.10				
					36388	2	38.00	39.00	1.00	0.01	0.10				
					36389	2	39.00	40.00	1.00	0.01	0.10				
					36391	2	40.00	41.00	1.00	0.01	0.10				
					36392	2	41.00	42.00	1.00	0.01	0.10				
37.30	70.83	Siltstone	SILT	light grey, very fine grained, banded at 30 CA; 1-2 % disseminated pyrite	36393	2	42.00	43.00	1.00	0.01	0.30				
					36394	2	43.00	44.00	1.00	0.01	0.40				
					36395	2	44.00	45.00	1.00	0.03	3.30				
					36396	2	45.00	46.00	1.00	0.01	4.90				
					36397	2	46.00	47.00	1.00	0.01	3.30				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					36398	2	47.00	48.00	1.00	0.01	1.90				
					36401	2	48.00	49.00	1.00	0.01	0.90				
					36402	2	49.00	50.00	1.00	0.01	1.50				
					36403	2	50.00	51.00	1.00	0.01	1.00				
					36404	2	51.00	52.00	1.00	0.01	0.10				
					36405	2	52.00	53.00	1.00	0.01	0.10				
					36406	2	53.00	54.00	1.00	0.01	0.10				
					36407	2	54.00	55.00	1.00	0.01	0.30				
					36408	2	55.00	56.00	1.00	0.01	0.30				
					36409	2	56.00	57.00	1.00	0.03	0.40				
					36411	2	57.00	58.00	1.00	0.02	0.30				
					36412	2	58.00	59.00	1.00	0.01	0.30				
					36413	2	59.00	60.00	1.00	0.01	0.20				
					36414	2	60.00	61.00	1.00	0.01	0.10				
					36415	2	61.00	62.00	1.00	0.01	0.10				
					36416	2	62.00	63.00	1.00	0.01	0.10				
					36417	2	63.00	64.00	1.00	0.01	0.10				
					36418	2	64.00	65.00	1.00	0.01	0.10				
					36421	2	65.00	66.00	1.00	0.01	0.10				
					36422	2	66.00	67.00	1.00	0.01	0.10				
					36423	2	67.00	68.00	1.00	0.01	0.10				
					36424	2	68.00	69.00	1.00	0.01	0.10				
70.83	86.50	FP	FP	Feldspar Porphyry: light grey, fine grained groundmass, porphyritic, 2-5mm white feldspar phenocrysts; sharp contact at 50 and 80 CA; 1-3% pyrite	36425	2	69.00	70.00	1.00	0.01	0.80				
					36426	2	70.00	70.83	0.83	0.01	1.90				
					36427	2	70.83	72.00	1.17	0.01	1.60				
					36428	2	72.00	73.00	1.00	0.01	0.10				
					36429	2	73.00	74.00	1.00	0.01	0.10				
					36431	2	74.00	75.00	1.00	0.01	0.30				
					36432	2	75.00	76.00	1.00	0.01	0.40				
					36433	2	76.00	77.00	1.00	0.01	0.70				
					36434	2	77.00	78.00	1.00	0.01	1.90				
					36435	2	78.00	79.00	1.00	0.01	0.80				
					36436	2	79.00	80.00	1.00	0.01	1.70				
					36437	2	80.00	81.00	1.00	0.01	0.70				
					36438	2	81.00	82.00	1.00	0.01	0.30				
					36441	2	82.00	83.00	1.00	0.01	0.30				
					36442	2	83.00	84.00	1.00	0.02	0.10				
					36443	2	84.00	85.00	1.00	0.02	0.10				
					36444	2	85.00	86.00	1.00	0.01	0.10				
					36445	2	86.00	86.50	0.50	0.01	0.60				
					36446	2	86.50	87.00	0.50	0.02	0.80				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					36447	2	87.00	88.00	1.00	0.01	0.50				
					36448	2	88.00	89.00	1.00	0.01	0.70				
					36449	2	89.00	90.00	1.00	0.01	0.10				
					36451	2	90.00	91.00	1.00	0.01	0.10				
					36452	2	91.00	92.00	1.00	0.01	0.10				
					36453	2	92.00	93.00	1.00	0.01	0.30				
					36454	2	93.00	94.00	1.00	0.02	0.10				
					36455	2	94.00	95.00	1.00	0.01	0.10				
					36456	2	95.00	96.00	1.00	0.01	0.10				
					36457	2	96.00	97.00	1.00	0.01	0.10				
					36458	2	97.00	98.00	1.00	0.01	0.10				
					36461	2	98.00	99.00	1.00	0.01	0.10				
					36462	2	99.00	100.00	1.00	0.01	0.10				
86.50	119.24	Siltstone	SILT	as above: 3-5% disseminated pyrite	36463	2	100.00	101.00	1.00	0.01	0.10				
					36464	2	101.00	102.00	1.00	0.01	0.20				
					36465	2	102.00	103.00	1.00	0.01	0.30				
					36466	2	103.00	104.00	1.00	0.02	0.20				
					36467	2	104.00	105.00	1.00	0.01	0.10				
					36468	2	105.00	106.00	1.00	0.03	0.20				
					36469	2	106.00	107.00	1.00	0.02	0.10				
					36471	2	107.00	108.00	1.00	0.01	0.20				
					36472	2	108.00	109.00	1.00	0.01	0.10				
					36473	2	109.00	110.00	1.00	0.01	0.20				
					36474	2	110.00	111.00	1.00	0.01	0.40				
					36475	2	111.00	112.00	1.00	0.01	0.40				
119.24	156.14	Diabase	DIA	as above:	36476	2	112.00	113.00	1.00	0.01	0.30				
					36477	2	113.00	114.00	1.00	0.01	0.10				
					36478	2	114.00	115.00	1.00	0.01	0.10				
156.14	156.20	FZ	FZ	Fault Zone: strongly sheared quartz carbonate at 50 CA; strong chlorite alteration; minor gouge	36481	2	115.00	116.00	1.00	0.01	0.20				
					36482	2	116.00	117.00	1.00	0.01	0.20				
					36483	2	117.00	118.00	1.00	0.01	0.40				
156.20	201.00	DIA	DIA	as above: EOH core stored at Matachewan	36484	2	118.00	119.24	1.24	0.01	0.10				
Downhole Tests:															
	Depth	AZ	DIP												
	102	331.6	-49.2												
	153	338.9	-49												
	201	338.9	-47.3												

Opawica Explorations Inc.

Matachewan
 DDH#: OPW-07-009
 Az and Dip: 330/-45
 E.O.H: 150 m

GRID LOCATION: Powell Twp., Ontario
 GRID: OPW: 2W 3+05N
 UTM, type: 0521475E, 5312998N: Nad: 83 Zone: 17
 Elev.:

Claim: 374014
 Drill Company: Downing: NQ Core
 Start: July 22, 2007; End: July 23, 2007
 Logged by: Fred Sharpley

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
0.00	2.86		OVB												
2.86	9.80	Greywacke	GWE	light grey, fine grained, occasional pebble, weak banding locally at 40-50 CA;											
9.80	28.60	CGL	CGL	light grey, fine grained, pebbles siltstone < 10 cm,											
28.60	43.50	Greywacke	GWE	as above: medium grey; <1% pyrite	36485	1	37.00	38.00	1.00	0.16	0.30				
					36486	1	38.00	39.00	1.00	0.16	0.40				
					36487	1	39.00	40.00	1.00	0.07	0.30				
					36488	1	40.00	41.00	1.00	0.03	0.30				
					36489	1	41.00	42.00	1.00	0.03	0.30				
					36490	1	42.00	43.00	1.00	0.01	0.20				
					36491	1	43.00	43.50	0.50	0.46	0.40				
43.50	75.90	Greywacke	GWE	as above: dark grey;	36492	1	43.50	44.00	0.50	0.01	0.10				
					36493	1	44.00	45.00	1.00	0.21	0.30				
					36495	1	147.00	148.00	1.00	0.01	0.20				
					36496	1	148.00	149.00	1.00	0.01	0.10				
75.90	146.90	TALC	TALC	dark green-grey, very fine grained, strongly sheared at 50 CA; Talc-Chlorite Schist; sharp contact at 70 CA; numerous quartz carbonate veins at 50 CA	36497	1	149.00	150.00	1.00	0.01	0.10				
146.90	150.00	SYN	SYN	Syenite Porphyry: pale pink, fine grained groundmass, porphyritic, white feldspar phenocrysts <5mm sharp contact at 60 CA; <1% pyrite											
				EOH											
				core stored at Matachewan											
Downhole Tests:															
	Depth	AZ	DIP												
	51	331.6	-45.7												
	105	331.1	-45.2												
	150	329.2	-44.2												

Opawica Explorations Inc.

Matachewan
DDH#: OPW-07-010
Az and Dip: 150/-50
E.O.H: 201 m

GRID LOCATION: Powell Twp., Ontario
GRID: OPW: 6W 2+30S
UTM, type: 0521383E, 5312327N: Nad: 83 Zone: 17
Elev.:

Claim: 3006742
Drill Company: Downing: NQ Core
Start: July 23, 2007; End: July 25, 2007
Logged by: Fred Sharpley

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
0.00	1.90		OVB												
1.90	66.00	Siltstone	SILT	light grey, very fine grained, weak to moderately banded at 40 CA; traces of pyrite; numerous quartz carbonate veins at 70 CA	44107	2	66.00	67.00	1.00	0.01	0.10				
					44108	2	67.00	68.00	1.00	0.01	0.20				
					44109	2	68.00	69.00	1.00	0.01	0.10				
				13.0-15.0 50% core recovery, limonite stained; oxidized.	44110	2	69.00	70.00	1.00	0.01	0.10				
					44111	2	70.00	71.00	1.00	0.01	0.20				
					44112	2	71.00	72.00	1.00	0.01	0.10				
				18.6-22.0 core broken up; limonite, oxidized.	44113	2	72.00	73.00	1.00	0.08	0.30				
					44114	2	73.00	74.00	1.00	0.01	0.20				
				41.0-42.0 40% quartz carbonate breccia with disseminated pyrrhotite	44115	2	74.00	75.00	1.00	0.01	0.10				
					44117	1	75.00	76.00	1.00	0.01	0.20				
					44118	1	76.00	77.00	1.00	0.01	0.20				
66.00	96.97	Siltstone	SILT	66.0-70.0 brecciated with weak disseminated pyrrhotite	44119	1	77.00	78.00	1.00	0.01	0.10				
				1-3%	44120	1	78.00	79.00	1.00	0.01	0.10				
					44121	1	79.00	80.00	1.00	0.01	0.10				
					44122	1	80.00	81.00	1.00	0.01	0.10				
					44123	1	81.00	82.00	1.00	0.01	0.10				
					44124	4	82.00	83.00	1.00	0.01	0.10				
					44127	4	83.00	84.00	1.00	0.01	0.10				
				81.90-96.97 3-5% blebs of pyrrhotite	44128	4	84.00	85.00	1.00	0.01	0.20				
					44129	4	85.00	86.00	1.00	0.01	0.10				
					44130	4	86.00	87.00	1.00	0.01	0.10				
					44131	4	87.00	88.00	1.00	0.01	0.20				
					44132	4	88.00	89.00	1.00	0.01	0.10				
					44133	4	89.00	90.00	1.00	0.01	0.10				
					44134	4	90.00	91.00	1.00	0.02	0.10				
					44135	4	91.00	92.00	1.00	0.01	0.10				
					44137	4	92.00	93.00	1.00	0.01	0.10				
96.97	126.00	Siltstone	SILT	as above: non-brecciated	44138	4	93.00	94.00	1.00	0.01	0.10				
					44139	4	94.00	95.00	1.00	0.01	0.10				
126.00	174.00	Greywacke	GWE	medium grey, fine grained, numerous quartz carbonate veins at 70 CA; 1-2% pyrite	44140	4	95.00	96.00	1.00	0.01	0.10				
					44141	4	96.00	97.00	1.00	0.01	0.10				
					44142	2	126.00	127.00	1.00	0.01	0.10				
					44143	2	127.00	128.00	1.00	0.01	0.20				
					44144	2	128.00	129.00	1.00	0.01	0.20				
					44147	2	129.00	130.00	1.00	0.01	0.20				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					44148	2	130.00	131.00	1.00	0.01	0.10				
					44149	2	131.00	132.00	1.00	0.01	0.30				
					44150	3	132.00	133.00	1.00	0.01	0.20				
					44151	3	133.00	134.00	1.00	0.01	0.40				
					44152	3	134.00	135.00	1.00	0.01	0.40				
					44153	3	135.00	136.00	1.00	0.01	0.20				
					44154	3	136.00	137.00	1.00	0.01	0.30				
				137..0-138.0 weak to moderate foliation at 40 CA	44155	3	137.00	138.00	1.00	0.01	0.80				
					44157	2	168.00	169.00	1.00	0.02	0.20				
				139.1- 4 cm quartz carbonate vein at 50 CA; weakly sheared	44158	2	169.00	170.00	1.00	0.16	0.40				
					44159	2	170.00	171.00	1.00	0.73	1.40				
					44160	2	171.00	172.00	1.00	0.12	0.30				
				168.0-172.0 strongly foliated at 40-50 CA; numerous quartz carbonate veins; 1-2% disseminated pyrite	44161		172.00	173.00	1.00	0.01	0.10				
					44162		173.00	174.00	1.00	0.16	0.40				
					44163	1	174.00	175.00	1.00	0.15	0.10				
					44164	1	175.00	176.00	1.00	0.07	0.10				
					44167	1	176.00	177.00	1.00	0.01	0.10				
174.00	184.50	Syenite	SYN	pale pink, fine grained, massive uniform; contact at 20-40 CA; moderately magnetic; 1% disseminated pyrite; porphyritic; quartz veins at 175.95, 176.6, 176.96, 177.66, 178.1, 180.17, 180.1, 180.56, 180.63, 180.67, 181.25;	44168	1	177.00	178.00	1.00	0.33	0.20				
					44169	1	178.00	179.00	1.00	0.18	0.40				
					44170	1	179.00	180.00	1.00	0.62	1.10				
					44171	1	180.00	181.00	1.00	0.29	0.40				
					44172	1	181.00	182.00	1.00	0.11	0.20				
184.50	190.65	Lam	LAM	dark green, massive uniform, porphyritic with white feldspar phenocrysts;	44173	1	182.00	183.00	1.00	0.01	0.30				
					44174	1	183.00	184.00	1.00	0.33	0.50				
					44175	1	184.00	184.50	0.50	0.07	0.10				
					44177		184.50	185.00	0.50	0.28	0.40				
					44178		185.00	186.00	1.00	0.04	0.20				
					44179		186.00	187.00	1.00	0.12	0.20				
					44180		187.00	188.00	1.00	0.28	1.20				
					44181		188.00	189.00	1.00	0.06	0.40				
190.65	201.00	Greywacke	GWE	as above: traces of magnetism; <1% pyrite	44182		189.00	190.00	1.00	0.01	0.10				
					44183		190.00	190.65	0.65	0.13	0.80				
					44184		190.65	191.00	0.35	0.09	0.20				
					44187		191.00	192.00	1.00	0.01	0.10				
				EOH											
				core stored at Matachewan											
Downhole Tests:															
	Depth	AZ	DIP												
	51	149.6	-48.8												
	100	151.4	-48.8												
	150	153.8	-48.8												

Opawica Explorations Inc.

Matachewan

DDH#: OPW-07-011

Az and Dip: 150/-60

E.O.H: 351 m

GRID LOCATION: Powell Twp., Ontario

GRID: OPW: 2W 1+90N

UTM, type: 0521529E, 5312896N: Nad: 83 Zone: 17

Elev.:

Claim: L372910

Drill Company: Downing: NQ Core

Start: July 24, 2007; End: July 27, 2007

Logged by: Fred Sharpley

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
0.00	2.60		OVB												
2.60	197.60	SILTSTONE	SILT	Interbanded Siltstone and Argillite: strongly banded black argillite: banded at 20 to 40 CA; with light grey siltstone; 40% ARG and 60% SILT; some quartz carbonate veins at 40 CA.											
197.60	207.46	LAM	LAM	medium grey, fine grained, massive, uniform; abundant black biotite; sharp contact at 60 CA-1-2% disseminated pyrite	36612	2	197.60	198.00	0.40	0.01	0.20				
					36613	2	198.00	199.00	1.00	0.01	0.30				
					36614	2	199.00	200.00	1.00	0.01	0.30				
					36617	2	200.00	201.00	1.00	0.01	0.20				
					36618	2	201.00	202.00	1.00	0.01	0.30				
					36619	2	202.00	203.00	1.00	0.01	0.20				
					36620	2	203.00	204.00	1.00	0.01	0.30				
					36621	2	204.00	205.00	1.00	0.01	0.20				
					36622	2	205.00	206.00	1.00	0.01	0.10				
207.46	210.16	SILTSTONE	SILT	as above: contact at 50 CA	36623	2	206.00	207.00	1.00	0.01	0.20				
					36624	2	207.00	207.46	0.46	0.01	0.10				
					36625	1	207.46	208.00	0.54	0.01	0.30	0.011			
210.16	231.30	ARGILLITE	ARG	dark grey, very fine grained, strongly banded at 40 CA	36627	1	208.00	209.00	1.00	0.02	0.30	0.007			
					36628	1	209.00	210.16	1.16	0.01	0.20	0.003			
231.30	238.80	FP	FP	light grey, fine grained groundmass, porphyritic, white feldspar phenocrysts; <1% pyrite; minor quartz veins at 50 CA											
238.80	259.30	ARGILLITE	ARG	as above:											
259.30	351.00	DIORITE	MAF	dark grey, fine grained massive uniform, sharp contact at 10 CA; Mafic Volcanic undifferentiated or Diorite; trace chalcopyrite											
				EOH											
				core stored at Matachewan											

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
Downhole Tests:															
	Depth	AZ	DIP												
	54	148.3	-59												
	105	152.5	-59.2												
	153	155.7	-59.7												
	201	152.1	-59.2												
	255	148.5	-57.5												
	300	148.5	-57.5												
	351	148.4	-58												

Opawica Explorations Inc.

Matachewan
DDH#: OPW-07-012
Az and Dip: 150/-55
E.O.H: 300 m

GRID LOCATION: Powell Twp., Ontario
GRID: OPW: 6W 4+30N
UTM, type: 0521478E, 5312174N: Nad: 83 Zone: 17
Elev.:

Claim: 3006742
Drill Company: Downing: NQ Core
Start: July 25, 2007; End: July 28, 2007
Logged by: Fred Sharpley

From	To	Rock Type	Code	Description	Sample#	%														
						Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %					
0.00	1.20		OVB																	
1.20	51.60	Diabase	DIA	medium grey, medium grained, massive, uniform; ophitic texture; xenoliths of siltstone < 2 cm	44001	4	162.34	162.53	0.19	0.01	0.10	0.039	0.000	0.008						
					44002	4	162.53	163.00	0.47	0.07	0.30	0.022	0.001	0.007						
					44003	4	163.00	164.00	1.00	0.08	0.30	0.020	0.001	0.007						
					44004	4	164.00	165.00	1.00	0.01	0.20	0.009	0.000	0.006						
				42.140-42.30 Feldspar Porphyry: pikish color, medium grained groundmass, coarse grained feldspar phenocrysts; contact at 70 CA	44005	4	165.00	166.00	1.00	0.01	0.20	0.013	0.000	0.006						
					44006	4	166.00	167.00	1.00	0.03	0.40	0.013	0.001	0.006						
					44007	4	167.00	168.00	1.00	0.01	0.30	0.007	0.000	0.004						
					44008	4	168.00	169.00	1.00	0.01	0.10	0.009	0.000	0.004						
51.60	52.10	Fault Zone	FZ	strongly sheared at 70 CA	44009	4	169.00	170.00	1.00	0.01	0.30	0.019	0.000	0.004						
					44011	4	170.00	171.00	1.00	0.01	0.30	0.014	0.000	0.005						
52.10	162.34	Diabase	DIA	as above:	44012	4	171.00	172.00	1.00	0.01	0.20	0.008	0.000	0.005						
					44013	4	172.00	173.00	1.00	0.01	0.10	0.014	0.001	0.005						
				90.0-90.10 quartz carbonate breccia at 40 CA	44014	4	173.00	174.00	1.00	0.01	0.30	0.006	0.003	0.006						
					44015	4	174.00	175.00	1.00	0.02	0.30	0.009	0.002	0.005						
				109.54-109.68 Feldspar Porphyry: light grey; contact at 70 CA	44016	4	175.00	176.00	1.00	0.04	0.40	0.005	0.003	0.005						
					44017	4	176.00	177.00	1.00	0.01	0.40	0.003	0.002	0.005						
					44018	4	177.00	178.00	1.00	0.01	0.30	0.011	0.001	0.004						
				118.62-118.77 Feldspar Porphyry: as above:	44021	4	178.00	179.00	1.00	0.05	0.20	0.011	0.003	0.005						
					44022	4	179.00	180.00	1.00	0.01	0.50	0.017	0.004	0.012						
				147.95-148.1 Feldspar Porphyry: as above: contact at 40 CA	44023	4	180.00	181.00	1.00	0.01	0.50	0.027	0.002	0.009						
					44024	4	181.00	182.00	1.00	0.01	0.50	0.016	0.001	0.005						
					44025	4	182.00	183.00	1.00	0.01	0.30	0.013	0.000	0.005						
162.34	162.53	Fault Zone	FZ	strongly shear quartz carbonate at 70 CA	44026	4	183.00	184.00	1.00	0.01	0.30	0.013	0.000	0.004						
					44027	4	184.00	185.00	1.00	0.07	0.30	0.014	0.001	0.005						
162.53	204.00	CGL	CGL	light grey, fine grained, uniform, 3-5% disseminated pyrite; Sulphide Zone: target; cobbles of siltstone, greywacke < 2 cm	44028	4	185.00	186.00	1.00	0.02	0.30	0.012	0.001	0.005						
					44029	4	186.00	187.00	1.00	0.02	0.20	0.013	0.000	0.005						
					44031	4	187.00	188.00	1.00	0.01	0.20	0.007	0.000	0.004						
					44032	4	188.00	189.00	1.00	0.01	0.20	0.006	0.001	0.006						
					44033	4	189.00	190.00	1.00	0.01	0.30	0.016	0.001	0.004						
					44034	4	190.00	191.00	1.00	0.02	0.20	0.009	0.000	0.004						
					44035	4	191.00	192.00	1.00	0.01	0.10	0.003	0.001	0.004						
				192.6 2 cm quartz carbonate vein at 50 CA; hematized trace of sphalerite	44036	4	192.00	193.00	1.00	0.05	0.20	0.009	0.000	0.004						
					44037	4	193.00	194.00	1.00	0.01	0.30	0.014	0.001	0.004						
					44038	4	194.00	195.00	1.00	0.01	0.20	0.013	0.000	0.004						

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					44041	4	195.00	196.00	1.00	0.01	0.20	0.007	0.000	0.004	
					44042	4	196.00	197.00	1.00	0.05	0.30	0.005	0.001	0.008	
					44043	4	197.00	198.00	1.00	0.01	0.30	0.004	0.003	0.010	
					44044	4	198.00	199.00	1.00	0.07	1.50	0.006	0.099	0.060	
					44045	4	199.00	200.00	1.00	0.01	0.20	0.011	0.003	0.010	
					44046	4	200.00	201.00	1.00	0.01	0.20	0.015	0.002	0.009	
					44047	4	201.00	202.00	1.00	0.01	0.10	0.017	0.002	0.014	
					44048	4	202.00	203.00	1.00	0.01	0.10	0.003	0.002	0.007	
					44049	4	203.00	204.00	1.00	0.13	0.40	0.003	0.006	0.016	
				198.30-198.55 quartz carbonate vein at 50 CA; trace pyrite, trace of sphalerite	44051	3	204.00	205.00	1.00	0.04	0.10	0.001	0.002	0.006	
				200.0 3 cm quartz carbonate vein at 50 CA; traces pyrite and sphalerite	44052	3	205.00	206.00	1.00	0.15	0.30	0.003	0.006	0.007	
					44053	3	206.00	207.00	1.00	0.01	0.10	0.001	0.002	0.006	
					44054	3	207.00	208.00	1.00	0.01	0.10	0.003	0.004	0.007	
				200.9 3 cm quartz carbonate vein at 50 CA; traces pyrite and sphalerite	44055	3	208.00	209.00	1.00	0.02	0.10	0.008	0.009	0.014	
					44056	3	209.00	210.00	1.00	0.01	0.10	0.008	0.002	0.022	
					44057	3	210.00	211.00	1.00	0.01	0.30	0.012	0.006	0.027	
204.00	276.00	CGL	CGL	as above: 1% disseminated pyrite: weak chlorite alt. Ser	44058	3	211.00	212.00	1.00	0.01	0.40	0.017	0.006	0.042	
				205.70-205.90 quartz carbonate vein at 20 CA; traces of pyrite	44061	3	212.00	213.00	1.00	0.01	0.10	0.007	0.003	0.011	
					44062	3	213.00	214.00	1.00	0.01	0.10	0.002	0.002	0.008	
					44063	3	214.00	215.00	1.00	0.01	0.10	0.002	0.002	0.008	
					44064	3	215.00	216.00	1.00	0.02	0.40	0.002	0.003	0.008	
					44065	3	216.00	217.00	1.00	0.01	0.30	0.032	0.002	0.010	
					44066	3	217.00	218.00	1.00	0.01	0.10	0.018	0.000	0.006	
					44067	3	218.00	219.00	1.00	0.01	0.10	0.014	0.000	0.006	
					44068	3	219.00	220.00	1.00	0.01	0.10	0.006	0.000	0.006	
				215.75-215.85 quartz carbonate vein at 30 CA; traces pyrite	44069	3	220.00	221.00	1.00	0.01	0.20	0.008	0.003	0.006	
					44071	2	221.00	222.00	1.00	0.01	0.10	0.006	0.000	0.005	
					44072	2	222.00	223.00	1.00	0.01	0.10	0.011	0.001	0.007	
					44073	2	223.00	224.00	1.00	0.01	0.10	0.001	0.000	0.004	
					44074	2	224.00	225.00	1.00	0.01	0.10	0.001	0.002	0.007	
					44075	2	225.00	226.00	1.00	0.01	0.10	0.016	0.000	0.006	
					44076	2	226.00	227.00	1.00	0.05	0.20	0.014	0.001	0.004	
					44077	2	227.00	228.00	1.00	0.04	0.40	0.008	0.003	0.004	
					44078	2	228.00	229.00	1.00	0.01	0.30	0.009	0.001	0.004	
					44081	2	229.00	230.00	1.00	0.01	0.20	0.024	0.001	0.004	
					44082	2	230.00	231.00	1.00	0.03	0.10	0.021	0.000	0.005	
					44083	2	231.00	232.00	1.00	0.08	0.30	0.030	0.001	0.004	
					44084	2	232.00	233.00	1.00	0.06	0.20	0.017	0.001	0.006	
					44085	2	233.00	234.00	1.00	0.01	0.10	0.014	0.000	0.007	
				268.55-268.85 moderately sheared quartz carbonate vein at 30 CA	44086	2	234.00	235.00	1.00	0.01	0.10	0.011	0.000	0.007	
					44087	2	235.00	236.00	1.00	0.03	0.10	0.011	0.000	0.013	

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
276.00	280.95	CGL	CGL	as above: no alteration: 1% disseminated pyrite	44088	2	236.00	237.00	1.00	0.06	0.10	0.015	0.001	0.006	
					44089	2	237.00	238.00	1.00	0.01	0.10	0.002	0.001	0.005	
					44091	1	238.00	239.00	1.00	0.01	0.10				
280.95	281.70	Fault Zone	FZ	moderately sheared quartz carbonate chlorite at 60 CA	44092	1	239.00	240.00	1.00	0.01	0.20				
					44093	1	240.00	241.00	1.00	0.01	0.20				
281.70	289.65	CGL	CGL	as above: 1% disseminated pyrite, traces chalcopyrite	44094	1	241.00	242.00	1.00	0.01	0.40				
					44095	1	242.00	243.00	1.00	0.05	0.70				
				traces chalcopyrite at 282.2, 284.05	44096	1	243.00	244.00	1.00	0.01	0.30				
					44097	1	244.00	245.00	1.00	0.01	0.40				
289.65	293.80	SYENITE	SYN	pale pinkish, very fine grained, massive, sharp contact at 20 CA	44098	1	245.00	246.00	1.00	0.01	0.40				
					44101	1	246.00	247.00	1.00	0.01	0.80				
					44102	1	247.00	248.00	1.00	0.13	1.00				
					44103	1	280.95	282.00	1.05	0.01	0.30	0.037			
					44104	1	282.00	283.00	1.00	0.01	0.40	0.041			
293.80	300.00	CGL	CGL	as above: <1% disseminated pyrite	44105	1	283.00	284.00	1.00	0.01	0.30	0.025			
					44106	1	284.00	285.00	1.00	0.02	0.10	0.018			
				EOH											
				core stored at Matachewan											
Downhole Tests:															
	Depth	AZ	DIP												
	51	152.1	-56.2												
	100	151	-56.1												
	150	151.2	-56.5												
	201	151.8	-56.5												
	300	155.6	-56.5												

Opawica Explorations Inc.

Matachewan
 DDH#: OPW-07-013
 Az and Dip: 150/-57
 E.O.H: 252 m

GRID LOCATION: Powell Twp., Ontario
 GRID: OPW: 4W 3+25N
 UTM, type: 0521288E, 5312918N: Nad: 83 Zone: 17
 Elev.:

Claim: L372910
 Drill Company: Downing: NQ Core
 Start: July 27, 2007; End: July 30, 2007
 Logged by: Fred Sharpley

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
0.00	3.90		OVB												
3.90	16.20	SILTSTONE	SILT	light grey, fine grained, weakly banded at 50 CA											
16.20	19.80	GWE	GWE	medium grey, moderate to strong sericite alteration; 1-2% pyrite	36629	1	16.20	17.00	0.80	0.14	0.40	0.006			
					36630	1	17.00	18.00	1.00	0.09	0.30	0.007			
					36631	1	18.00	19.00	1.00	0.13	0.10	0.007			
					36632	1	19.00	19.80	0.80	0.03	0.20	0.005			
					36633		19.80	21.00	1.20	0.01	0.30	0.005			
					36634		21.00	22.00	1.00	0.01	0.30	0.007			
					36637	1	113.50	114.00	0.50	0.45	1.00	0.006			
					36638	1	114.00	115.00	1.00	0.38	0.60	0.007			
				33.0 5cm quartz vein at 80 CA	36639	1	115.00	116.00	1.00	0.31	0.50	0.007			
					36640	1	116.00	117.00	1.00	0.03	0.20	0.008			
				34.6 4 cm quartz vein at 60 CA	36641	1	117.00	118.00	1.00	0.29	0.70	0.007			
					36642	1	118.00	119.00	1.00	0.15	0.50	0.008			
19.80	51.00	GWE	GWE	as above: unaltered; minor interbanded argillite 41.5-44.0 weak sericite alteration	36643	1	119.00	120.00	1.00	0.01	0.30	0.009			
					36644	1	120.00	121.00	1.00	0.01	0.20	0.007			
51.00	58.50	ARGILLITE	ARG	Interbanded Argillite and Siltstone 60-40%; banded at 30 CA; numerous quartz carbonate veins at 30-40 CA	36645	1	121.00	122.00	1.00	0.02	0.30	0.008			
					36647		133.00	134.00	1.00	0.01	0.40	0.017			
58.50	85.40	SILTSTONE	SILT	as above: traces of pyrite	36648	1	150.00	151.00	1.00	0.03	0.40	0.006			
				83.6-85.4 Diorite Dike: pale green, fine grained massive uniform; contact at 20-40 CA	36649	1	151.00	152.00	1.00	0.47	0.30	0.006			
					36650	1	152.00	153.00	1.00	0.28	0.60	0.009			
85.40	89.30	ARGILLITE	ARG	as above: banded at 40 CA	36651	1	153.00	154.00	1.00	0.02	0.30	0.004			
					36652	1	154.00	155.00	1.00	0.01	0.20	0.004			
89.30	94.00	SILTSTONE	SILT	as above	36653	1	155.00	156.00	1.00	0.01	0.20	0.006			
					36654	1	156.00	157.00	1.00	0.01	0.20	0.005			
94.00	101.60	DIORITE	DIO	as above:	36657	1	157.00	158.00	1.00	0.04	0.60	0.007			
					36658	1	158.00	159.00	1.00	0.11	0.50	0.004			
101.60	133.00	SILTSTONE	SILT	as above:	36659	1	159.00	160.00	1.00	0.01	0.30	0.004			
					36660	1	160.00	161.00	1.00	0.05	0.40	0.006			
				113.50-118.6 1% disseminated pyrite; numerous slips at 30-40 CA; bleached, weak sericite alteration.	36661	1	161.00	162.00	1.00	0.01	0.20	0.004			
					36662	1	162.00	163.00	1.00	0.11	0.20	0.006			
					36663	1	163.00	164.00	1.00	0.13	0.40	0.008			
					36664	1	164.00	165.00	1.00	0.04	0.30	0.007			

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					36665	1	165.00	166.00	1.00	0.01	0.10	0.006			
				130.00 10 cm quartz vein at 40 CA	36667	1	166.00	167.00	1.00	0.01	0.50	0.010			
					36668	1	167.00	168.00	1.00	0.04	0.30	0.008			
133.00	153.75	ARGILLITE	ARG	as above:	36669	1	168.00	169.00	1.00	0.01	0.40	0.005			
					36670	1	169.00	170.00	1.00	0.10	0.70	0.005			
				133.00-134.00 20% quartz veining at 40 CA	36671	1	170.00	171.00	1.00	0.14	0.70	0.006			
					36672	1	171.00	172.00	1.00	0.01	0.20	0.007			
153.75	161.30	SILTSTONE	SILT	as above:	36673	1	172.00	173.00	1.00	0.01	0.40	0.007			
					36674	1	190.00	191.00	1.00	0.01	0.30	0.004			
					36677	1	191.00	192.00	1.00	0.01	0.10	0.004			
					36678	1	192.00	193.00	1.00	0.22	0.70	0.004			
161.30	169.50	ARGILLITE	ARG	as above: 1% pyrite	36679	1	193.00	194.00	1.00	0.04	0.50	0.008			
					36680	1	194.00	195.00	1.00	0.01	0.10	0.006			
					36681	1	195.00	196.00	1.00	0.04	0.10	0.005			
169.50	174.00	SILTSTONE	SILT	as above:	36682	1	196.00	197.00	1.00	0.01	0.10	0.005			
					36683	1	197.00	198.00	1.00	0.01	0.20	0.005			
					36684	1	198.00	199.00	1.00	0.07	0.20	0.005			
174.00	176.00	ARGILLITE	ARG	as above:	36685	1	199.00	200.00	1.00	0.06	0.30	0.006			
					36687	1	200.00	201.00	1.00	0.04	0.20	0.005			
176.00	201.10	SILTSTONE	SILT	as above:	36688	2	201.00	202.00	1.00	0.05	0.30	0.010			
					36689	2	202.00	203.00	1.00	0.08	0.60	0.010			
				190.0-195.0 weak disseminated pyrite	36690	1	203.00	204.00	1.00	0.07	0.30	0.009			
				192.00-194.5 bleached	36691	2	210.00	211.00	1.00	0.20	0.40	0.006			
				194.3 2 cm quartz vein at 50 CA	36692	2	211.00	212.00	1.00	0.19	0.30	0.003			
					36693	2	212.00	213.00	1.00	0.05	0.70	0.003			
					36694	2	213.00	214.00	1.00	0.01	0.20	0.005			
201.10	202.70	FP	FP	light grey, fine grained massive uniform, 2mm white feldspar phenocrysts; 1-2% disseminated pyrite											
202.70	252.00	SILTSTONE	SILT	as above:											
				210.00-213.00 strong sericite alteration; 2-3% disseminated pyrite											
				245.0 trace of chalcopyrite											
				252.00 EOH											
				core stored at Matachewan											

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
Downhole Tests:															
	Depth	AZ	DIP												
	54	151.2	-56.3												
	105	153.7	-56.8												
	140	157	-54.3												
	201	158.4	-54.3												
	252	160	-53.1												

Opawica Explorations Inc.

Matachewan
DDH#: OPW-07-014
Az and Dip: 150/-70
E.O.H: 300 m

GRID LOCATION: Powell Twp., Ontario
GRID: OPW: 6W 8+00S
UTM, type: 0521657E, 5311835N: Nad: 83 Zone: 17
Elev.: 363

Claim: L372904
Drill Company: Downing: NQ Core
Start: July 29, 2007; End: July 31, 2007
Logged by: Fred Sharpley

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
0.00	2.40		OVB												
					36805	2	20.00	21.00	1.00	0.08	0.80				
2.40	6.00	CGL	CGL	medium grey, fine grained, cobbles of siltstone, greywacke <6 cm; weakly banded at 40 CA;	36806	2	21.00	22.00	1.00	0.02	0.60				
					36807	2	22.00	23.00	1.00	0.12	0.70				
					36808	2	23.00	24.00	1.00	0.29	1.80				
6.00	10.86	Greywacke	GWE	medium grey, fine grained, massive;	36809	2	24.00	24.40	0.40	0.11	0.70				
					36810	1	24.40	25.00	0.60	0.21	0.70				
					36811	1	25.00	26.00	1.00	1.78	6.60				
10.86	22.66	CGL	CGL	as above:	36812	1	26.00	27.00	1.00	0.06	0.50				
				20.0-23.0 2-3%disseminations and blebs of pyrite	36813	1	27.00	28.00	1.00	0.03	0.10				
22.66	24.40	Greywacke	GWE	as above:	36815	1	28.00	29.00	1.00	0.03	0.10				
					36816	1	29.00	30.00	1.00	0.01	0.10				
24.40	37.30	FP	FP	medium grey, fine grained groundmass, coarse pink feldspar phenocrysts <2cm; massive uniform; contact at 40-50 CA;	36817	1	30.00	31.00	1.00	0.02	0.10				
					36818	1	31.00	32.00	1.00	0.02	0.20				
					36819	1	32.00	33.00	1.00	0.03	0.30				
					36820	1	33.00	34.00	1.00	0.04	0.30				
				25.4-26.3 greywacke; 2-3% pyrite	36821	1	34.00	35.00	1.00	0.01	0.10				
					36822	1	35.00	36.00	1.00	0.01	0.10				
					36825	1	36.00	37.30	1.30	0.01	0.40				
					36826	1	37.30	38.00	0.70	0.54	1.40				
37.30	41.00	CGL	CGL	as above:	36827	2	41.00	42.00	1.00	0.08	0.30				
					36828	2	42.00	43.00	1.00	0.23	1.10				
41.00	45.00	Greywacke	GWE	as above: 1-3% disseminated pyrite	36829	2	43.00	44.00	1.00	0.01	0.80				
					36830	2	44.00	45.00	1.00	0.01	0.50				
					36831	1	45.00	46.00	1.00	0.01	0.40				
					36832	1	46.00	47.00	1.00	0.03	0.50				
45.00	49.30	CGL	CGL	as above:	36833	1	47.00	48.00	1.00	0.01	0.30				
					36835	1	48.00	49.30	1.30	0.01	0.60				
					36836	1	49.30	50.00	0.70	0.01	0.70				
49.30	50.84	SYN	SYN	dark pinkish green, fine grained massive, uniform; sharp contact at 30 and 60 CA	36837	1	50.00	50.84	0.84	0.04	0.30				
					36838	1	50.84	52.00	1.16	0.03	0.60				
					36839	3	74.00	75.00	1.00	0.04	0.40				
50.80	183.90	CGL	CGL	as above: cobbles including syenite <6cm	36840	3	75.00	76.00	1.00	0.07	0.30				
					36841	3	76.00	77.00	1.00	0.11	0.40				
					36842	3	77.00	78.00	1.00	0.08	0.40				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
				59.0-60.3 numerous quartz carbonate veinlets at 50 CA	36845	3	78.00	79.00	1.00	0.03	0.10				
					36846	1	116.00	117.00	1.00	0.37	1.70				
				74.0-79.0 3-5% disseminated pyrite	36847	1	117.00	118.00	1.00	0.29	1.60				
					36848	1	118.00	119.00	1.00	0.10	0.40				
					36849	1	119.00	120.00	1.00	0.09	0.50				
				117.25-117.50 quartz carbonate veining at 40 CA; disseminated pyrite	36850	1	120.00	121.00	1.00	0.54	1.80				
					36851	1	121.00	122.00	1.00	0.14	0.50				
					36852	1	122.00	123.00	1.00	0.23	0.20				
					36853	1	123.00	124.00	1.00	0.07	0.30				
				128.0-135.0 1% disseminated pyrite	36855	1	128.00	129.00	1.00	0.01	0.70				
					36856	1	129.00	130.00	1.00	0.04	0.20				
					36857	1	130.00	131.00	1.00	0.05	0.50				
				137.0- 7cm quartz vein at 70 CA	36858	1	131.00	132.00	1.00	0.15	0.40				
					36859	1	132.00	133.00	1.00	0.05	0.30				
					36860	1	133.00	134.00	1.00	0.03	0.30				
				158.0 3 cm quartz vein at 70 CA	36861	1	134.00	135.00	1.00	0.03	0.20				
				159.06 3 cm Quartz vein at 70 CA	36862		135.00	136.00	1.00	0.02	0.50				
					36865		136.00	137.00	1.00	0.04	0.20				
				182.5-183.0 quartz carbonate breccia; disseminated py	36866		137.00	138.00	1.00	0.01	0.20				
					36867	2	182.00	183.00	1.00	2.32	1.30	0.060			
183.90	216.10	SYN	SYN	Syenite Porphyry: pale pinkish green, fine grained, groundmass, coarse grained phenocrysts, <1 cm 1% disseminated pyrite	36868	1	183.00	183.90	0.90	0.17	0.70	0.097			
					36869	1	183.90	185.00	1.10	0.08	0.80	0.033			
					36870	1	185.00	186.00	1.00	0.04	0.50	0.084			
					36871	1	186.00	187.00	1.00	0.07	1.40	0.059			
					36872	1	187.00	188.00	1.00	0.09	0.30	0.051			
				191.5-192.18 10% quartz veining	36873	1	188.00	189.00	1.00	0.09	0.90	0.063			
				192.05 4 cm bleb of chalcopyrite, galena	36875	1	189.00	190.00	1.00	0.01	0.50	0.051			
					36876	1	190.00	191.00	1.00	0.11	0.60	0.045			
					36877	1	191.00	192.00	1.00	0.01	0.70	0.016			
				199.23 1 cm quartz vein at 60 CA	36878	1	192.00	193.00	1.00	0.10	7.90	0.315			
					36879	1	193.00	194.00	1.00	0.01	0.50	0.051			
					36880	1	194.00	195.00	1.00	0.01	0.60	0.031			
				203.0 1 cm quartz vein at 60 CA	36881	1	195.00	196.00	1.00	0.01	0.20	0.014			
					36882	1	196.00	197.00	1.00	0.01	0.10	0.009			
					36885	1	197.00	198.00	1.00	0.01	0.40	0.045			
216.10	241.20	CGL	CGL	as above:	36886	1	198.00	199.00	1.00	0.07	0.40	0.030			
					36887	1	199.00	200.00	1.00	0.03	0.20	0.034			
				225.0-300 strongly magnetic, probably magnetite	36888	1	200.00	201.00	1.00	0.01	0.30	0.027			
					36889	1	201.00	202.00	1.00	0.01	1.60	0.013			
241.20	243.15	LAM	LAM	medium green, fine grained, massive, uniform; sharp contact at 20 CA	36890	1	202.00	203.00	1.00	0.01	0.10	0.017			
					36891	1	203.00	204.00	1.00	0.01	0.30	0.024			
					36892	1	204.00	205.00	1.00	0.01	0.20	0.049			

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
243.15	244.40	FP	FP	as above:	36893	1	205.00	206.00	1.00	0.04	0.30	0.040			
					36894	1	206.00	207.00	1.00	0.17	1.50	0.167			
244.40	247.90	LAM	LAM	as above:	36895		256.00	257.00	1.00	0.05	0.20	0.029			
					36897		257.00	258.00	1.00	0.04	1.50	0.073			
247.90	250.84	FP	FP	as above:	36898		258.00	258.50	0.50	0.01	0.10	0.022			
					36899		258.50	259.00	0.50	0.01	0.10	0.029			
250.84	281.30	CGL	CGL	as above: strong magnetite											
				257.0-258.26 quartz with pink feldspar at 20 CA; trace blobs of chalcopyrite											
				279.70-280.0 Feldspar Porphyry: contact at 40 & 60 CA											
281.30	285.10	SYN	SYN	as above: fine grained phenocrysts; contact at 60 CA mixed with Lamprophyre: LAM 281.3 2 cm quartz vein at 60 CA											
285.10	296.60	CGL	CGL	as above: magnetite											
296.60	297.66	SYN	SYN	Syenite Porphyry: as above:											
297.66	300.00	Greywacke	GWE	as above:											
				EOH											
				core stored at Matachewan											
Downhole Tests:															
	Depth	AZ	DIP												
	54	154.9	-70.5												
	150	157.5	-70.8												
	201	158.6	-70.5												
	300	165.5	-70												

Opawica Explorations Inc.

Matachewan
DDH#: OPW-07-015
Az and Dip: 330/-60
E.O.H: 201 m

GRID LOCATION: Powell Twp., Ontario
GRID: OPW:6W 2+95N
UTM, type: 0521129E, 5312796N: Nad: 83 Zone: 17
Elev.:

Claim: L372911
Drill Company: Downing: NQ Core
Start: July 30, 2007; End: July 31, 2007
Logged by: Fred Sharpley

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
0.00	4.00		OVB												
4.00	50.30	Diabase	DIA	medium grey, massive uniform, medium grained, ophitic texture											
50.30	79.00	Mafic	MAF	fine grained, medium grey, massive uniform; possible mafic volcanics or greywacke	36695	3	51.00	52.00	1.00	0.01	0.20	0.019			
					36698	3	52.00	53.00	1.00	0.01	0.10	0.012			
					36699	3	53.00	54.00	1.00	0.01	0.10	0.008			
				51.0-56.0 weak to moderate disseminated pyrite;	36700	3	54.00	55.00	1.00	0.01	0.10				
					36701	3	55.00	56.00	1.00	0.01	0.10				
					36702		98.00	98.80	0.80	0.01	0.20				
					36703	1	98.80	99.00	0.20	0.01	0.10				
					36704	1	99.00	100.00	1.00	0.01	0.10				
79.00	98.80	Diabase	DIA	as above: contact at 20 CA; numerous slip at contact	36705	3	100.00	101.00	1.00	0.02	0.10				
					36706	3	101.00	101.60	0.60	0.14	0.10				
98.80	101.60	Mafic	MAF	as above: 1-3% disseminated pyrite	36708		101.60	102.00	0.40	0.03	0.20				
					36709		126.60	127.00	0.40	0.01	0.10				
					36710		127.00	128.00	1.00	0.01	0.10				
					36711		128.00	129.00	1.00	0.01	0.10				
101.60	133.50	Diabase	DIA	as above: sharp contact at 60 CA	36712		129.00	130.00	1.00	0.01	0.10				
				126.60-133.50 numerous quartz carbonate veins at 60 CA	36713		130.00	131.00	1.00	0.01	0.10				
					36714		131.00	132.00	1.00	0.01	0.10				
					36715		132.00	133.00	1.00	0.01	0.10				
				127.70 4 cm quartz vein at 70 CA	36718		133.00	133.50	0.50	0.01	0.10				
					36719	1	133.50	134.00	0.50	0.01	0.10				
					36720	1	134.00	135.00	1.00	0.01	0.10				
					36721	1	135.00	136.00	1.00	0.01	0.10				
133.50	201.00	Greywacke	GWE	light to medium grey, very fine grained, weakly banded at 40-50 CA; numerous quartz carbonate veinlets. minor argillite	36722	1	136.00	137.00	1.00	0.01	0.10				
					36723	1	137.00	138.00	1.00	0.01	0.10				
					36724	1	138.00	139.00	1.00	0.01	0.10				
				core stored at Matachewan											
				EOH											

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
Downhole Tests:															
	Depth	AZ	DIP												
	54	332.5	-58.8												
	105	331.2	-59.1												
	153	334.3	-59.1												
	201	336.2	-58.8												

Opawica Explorations Inc.

Matachewan
 DDH#: OPW-07-016
 Az and Dip: 150/-60
 E.O.H: 300 m

GRID LOCATION: Powell Twp., Ontario
 GRID: OPW:2W 4+10S
 UTM, type: 0521820E, 5312371N: Nad: 83 Zone: 17
 Elev.:

Claim: L372901
 Drill Company: Downing: NQ Core
 Start: August 01, 2007; End: August 03, 2007
 Logged by: Fred Sharpley

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
0.00	2.00		OVB												
					36725	1	50.00	51.00	1.00	0.03	0.40				
2.00	93.55	Greywacke	GWE	medium grey, very fine grained, fairly massive	36726	1	51.00	52.00	1.00	0.03	0.10				
					36727	2	58.00	59.00	1.00	0.05	0.30				
				50.0-51.7 60% quartz carbonate breccia at 30 CA; 1-2% disseminated pyrite	36728	2	59.00	60.00	1.00	0.04	0.40				
					36729	2	60.00	61.00	1.00	0.07	0.40				
					36731	2	61.00	62.00	1.00	0.90	0.50				
				58.0-70.0 1-3% disseminated pyrite	36732	2	62.00	63.00	1.00	0.10	0.30				
					36733	2	63.00	64.00	1.00	0.22	0.30				
					36734	2	64.00	65.00	1.00	0.46	0.10				
					36735	2	65.00	66.00	1.00	0.13	0.40				
				90.8 4 cm massive pyrite vein with quartz carbonate vein at 20 CA; 60% pyrite	36736	2	66.00	67.00	1.00	0.46	0.50				
					36737	2	67.00	68.00	1.00	0.07	0.40				
					36738	2	68.00	69.00	1.00	0.03	0.40				
93.55	106.65	CGL	CGL	medium grey matrix with pebbles of siltstone <2 cm	36741	2	69.00	70.00	1.00	0.17	0.50				
					36742	2	90.00	91.00	1.00	0.07	0.40				
					36743	2	91.00	92.00	1.00	0.03	0.30				
106.65	116.00	Greywacke	GWE	as above:	36744	2	114.00	115.00	1.00	0.15	0.30				
					36745	2	115.00	116.00	1.00	0.01	0.60				
116.00	125.00	CGL		as above:	36746	2	116.00	117.00	1.00	0.11	0.50				
				114.0-123.0 1-2% disseminated pyrite	36747	2	117.00	118.00	1.00	0.01	0.80				
					36748	2	118.00	119.00	1.00	0.01	0.40				
					36749	2	119.00	120.00	1.00	0.01	0.30				
125.00	133.00	Greywacke	GWE	as above:	36751	2	120.00	121.00	1.00	0.01	0.20				
					36752	2	121.00	122.00	1.00	0.06	0.40				
					36753	2	122.00	123.00	1.00	0.01	0.30				
133.00	140.90	CGL	CGL	as above:	36754	1	140.00	141.00	1.00	0.03	0.30				
					36755	1	141.00	142.00	1.00	0.01	0.30				
140.90	145.00	Greywacke	GWE	as above:	36756	1	142.00	143.00	1.00	0.09	0.40				
				145.0- 4 cm quartz carbonate slip at 50 CA; diss py	36757	1	143.00	144.00	1.00	0.04	0.40				
145.00	160.00	CGL	CGL	as above:	36758	1	144.00	145.00	1.00	0.05	0.40				
					36761	2	145.00	146.00	1.00	0.05	0.40				
					36762	2	146.00	147.00	1.00	0.01	0.30				
					36763	2	147.00	148.00	1.00	0.01	0.30				
160.00	192.38	Greywacke	GWE	as above:	36764	2	148.00	149.00	1.00	0.01	0.20				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					36765	2	149.00	150.00	1.00	0.10	0.40				
				160.0-161.4 strong hematite alteration with moderate disseminated pyrite	36766	2	150.00	151.00	1.00	0.79	0.40				
					36767	2	151.00	152.00	1.00	0.19	0.30				
					36768	2	152.00	153.00	1.00	0.08	0.10				
192.38	204.40	CGL	CGL	as above: 1% disseminated pyrite	36769	2	153.00	154.00	1.00	0.12	0.10				
					36771	2	190.00	191.00	1.00	0.19	0.30				
				204.0-204.4 weakly sheared at 70 CA; quartz stringers with 2-3% disseminated pyrite	36772	2	191.00	192.00	1.00	0.01	0.10				
					36773	2	192.00	193.00	1.00	0.03	0.20				
				204.40-205.0 3-4 cm stringer of massive pyrite	36774	1	202.00	203.00	1.00	0.01	0.20				
					36775	1	203.00	204.00	1.00	0.14	0.10				
204.40	217.40	Greywacke	GWE	as above:	36776	3	204.00	204.40	0.40	0.10	0.60				
					36777	10	204.40	205.00	0.60	0.05	0.50				
					36778	2	205.00	206.00	1.00	0.04	0.20				
217.40	233.60	CGL	CGL	as above: weak hematite and epidote alteration; 1% disseminated pyrite	36781	1	206.00	207.00	1.00	0.03	0.10				
					36782	1	207.00	208.00	1.00	0.01	0.10				
					36783	1	208.00	209.00	1.00	0.03	0.10				
					36784	1	209.00	210.00	1.00	0.02	0.10				
					36785	1	217.40	218.00	0.60	0.04	0.10				
				225.5-226.5 30% quartz carbonate veining at 60 CA	36786	1	218.00	219.00	1.00	0.01	0.10				
					36787	1	219.00	220.00	1.00	0.01	0.10				
					36788	1	220.00	221.00	1.00	0.03	0.10				
					36789	1	221.00	222.00	1.00	0.01	0.10				
					36791	1	222.00	223.00	1.00	0.02	0.10				
					36792	1	223.00	224.00	1.00	0.04	0.10				
					36793	1	224.00	225.00	1.00	0.03	0.10				
					36794	1	225.00	226.00	1.00	0.07	0.20				
233.60	300.00	Diabase	DIA	dark grey, fine grained massive uniform; moderately magnetic; contact at 20 CA	36795	1	226.00	227.00	1.00	0.02	0.10				
					36796	1	227.00	228.00	1.00	0.01	0.10				
					36797	1	228.00	229.00	1.00	0.02	0.20				
					36798	1	229.00	230.00	1.00	0.04	0.20				
				276.0-285.9 coarse grained, porphyritic, white feldspar 2-3 cm	36801	1	230.00	231.00	1.00	0.01	0.10				
					36802	1	231.00	232.00	1.00	0.01	0.10				
					36803	1	232.00	233.00	1.00	0.03	0.10				
					36804	1	233.00	233.60	1.00	0.02	0.10				
				EOH											
				core stored at Matachewan											

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
Downhole Tests:															
	Depth	AZ	DIP												
	54	150.5	-54.8 ?												
	108	151.2	-60.3												
	153	152.5	-60												
	204	155.2	-59.3												
	255	158.9	-58.2												
	300	160.6	-57.5												

Opawica Explorations Inc.

Matachewan
DDH#: OPW-07-017
Az and Dip: 330/-50
E.O.H: 498 m

GRID LOCATION: Powell Twp., Ontario
GRID: OPW: 4W 9+70S
UTM, type: 0521912E, 5311782N: Nad: 83 Zone: 17
Elev.:

Claim: L372902
Drill Company: Downing: NQ Core
Logged by: Fred Sharpley
Start: August 01, 2007; End: August 09, 2007

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
0.00	2.10		OVB												
					44261	2	13.00	14.00	1.00	0.01	0.30				
2.10	49.40	CGL	CGL	light to medium grey, very fine grained, cobbles of siltstone, greywacke, argillite and iron formation;	44262	2	14.00	15.00	1.00	0.01	0.20				
				< 5 cm; magnetic locally	44263	2	15.00	16.00	1.00	0.05	0.30				
				13.0-19.0 1-3% disseminated pyrite	44264	2	16.00	17.00	1.00	0.11	0.30				
				14.0 quartz carbonate vein at 30 CA	44265	2	17.00	18.00	1.00	0.01	0.20				
					44266	2	18.00	19.00	1.00	0.08	0.50				
					44267	2	19.00	20.00	1.00	0.01	0.20				
					44268	2	20.00	21.00	1.00	0.02	0.20				
				32.0-36.0 1-2% disseminated pyrite	44271	2	32.00	33.00	1.00	0.04	0.20				
					44272	2	33.00	34.00	1.00	0.01	0.20				
					44273	2	34.00	35.00	1.00	0.03	0.10				
49.40	58.25	Lam	LAM	medium green, fine grained massive, uniform; contact at 50 CA; 70% lampriphyre and 30% conglomerate;	44274	2	35.00	36.00	1.00	0.01	0.30				
				traces chalcopryrite; 1% pyrite	44275	1	49.40	50.00	0.60	0.03	0.20	0.012			
					44276	1	50.00	51.00	1.00	0.07	0.20	0.012			
					44277	1	51.00	52.00	1.00	0.03	0.20	0.037			
58.25	97.00	SYN	SYN	Syenite Porphyry: pinkish grey, coarse grained pink feldspar phenocysts in a pinkish grey fine grained groundmass; contact at 60 CA; blebs and seams of chalcopryrite <1% with disseminated pyrite <1%	44278	1	52.00	53.00	1.00	0.06	0.30	0.042			
					44279	1	53.00	54.00	1.00	0.03	0.10	0.015			
					44281	1	54.00	55.00	1.00	0.05	0.30	0.050			
					44282	1	55.00	56.00	1.00	0.01	0.30	0.063			
					44283	1	56.00	57.00	1.00	0.13	0.30	0.064			
				58.25-86.0 strong red alteration: hemitization	44284	1	57.00	58.00	1.00	0.01	0.70	0.093			0.001
					44285	1	58.00	59.00	1.00	0.38	0.40	0.047			0.002
					44286	1	59.00	60.00	1.00	0.01	0.60	0.127			0.001
				79.0-80.0 dark grey groundmass; 1-2% pyrite	44287	1	60.00	61.00	1.00	0.01	0.20	0.055			0.000
					44288	1	61.00	62.00	1.00	0.04	0.50	0.170			0.001
					44291	1	62.00	63.00	1.00	0.01	0.60	0.127			0.001
					44292	1	63.00	64.00	1.00	0.71	1.90	0.041			0.001
					44293	1	64.00	65.00	1.00	0.04	0.40	0.077			0.000
					44294	1	65.00	66.00	1.00	0.09	0.70	0.117			0.002
					44295	1	66.00	67.00	1.00	0.05	0.60	0.050			0.001
					44296	1	67.00	68.00	1.00	0.38	1.80	0.003			0.002
					44297	1	68.00	69.00	1.00	0.07	0.80	0.058			0.001
				86.6-86.85 moderately foliated at 60 CA; 2% pyrite, traces chalcopryrite;	44298	1	69.00	70.00	1.00	0.04	0.60	0.013			0.000
					44299	1	70.00	71.00	1.00	0.01	0.20	0.005			0.000

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
				88.40-90.50 10% quartz veinlets at 40 to parallel CA;	44301	1	71.00	72.00	1.00	0.01	0.20	0.020			0.001
					44302	1	72.00	73.00	1.00	0.01	0.30	0.018			0.002
					44303	1	73.00	74.00	1.00	0.02	0.20	0.020			0.001
97.00	106.23	FP	FP	Feldspar Porphyry: as above but coarse grained phenocrysts in a medium grey groundmass; 1% pyrite	44304	1	74.00	75.00	1.00	0.01	0.40	0.025			0.000
					44305	1	75.00	76.00	1.00	0.01	0.20	0.019			0.001
					44306	1	76.00	77.00	1.00	0.01	0.40	0.020			0.000
				97.0-103 traces chalcopyrite with 10% quartz veinlets at 40 and 70 CA	44307	1	77.00	78.00	1.00	0.01	0.70	0.054			0.001
					44308	1	78.00	79.00	1.00	0.01	0.40	0.047			0.000
					44309	1	79.00	80.00	1.00	3.75	22.80	0.007			0.006
					44312	1	80.00	81.00	1.00	0.01	1.00	0.144			0.001
					44313	1	81.00	82.00	1.00	0.01	1.30	0.132			0.003
					44314	1	82.00	83.00	1.00	0.01	0.20	0.015			0.000
					44315	1	83.00	84.00	1.00	0.01	0.20	0.006			0.001
					44316	1	84.00	85.00	1.00	0.03	0.10	0.017			0.001
					44317	1	85.00	86.00	1.00	0.09	1.00	0.095			0.027
106.23	138.80	CGL	CGL	similar to above:	44318	1	86.00	87.00	1.00	0.08	0.80	0.097			0.003
				106.23-134.00 strong blebby magnetite, 5-10%; 2-3% disseminated pyrite, traces of chalcopyrite	44319	1	87.00	88.00	1.00	0.02	0.20	0.041			0.001
					44320	1	88.00	89.00	1.00	0.01	0.10	0.021			0.001
					44322	1	89.00	90.00	1.00	0.01	0.20	0.060			0.008
					44323	1	90.00	91.00	1.00	0.06	0.20	0.102			0.007
					44324	1	91.00	92.00	1.00	0.03	0.20	0.052			0.001
				121.7 2 cm quartz vein at 60 CA	44325	1	92.00	93.00	1.00	0.06	0.20	0.101			0.001
					44326	1	93.00	94.00	1.00	0.01	0.30	0.049			0.001
					44327	1	94.00	95.00	1.00	0.01	0.10	0.031			0.001
				117.50 5 cm quartz carbonate vein at 30 CA	44328	1	95.00	96.00	1.00	0.04	0.10	0.025			0.000
					44329	1	96.00	97.00	1.00	0.03	0.10	0.051			0.001
				126.00-134.00 numerous speckes of chalcopyrite	44332	1	97.00	98.00	1.00	0.03	0.10	0.045			0.001
					44333	1	98.00	99.00	1.00	0.01	0.20	0.070			0.001
					44334	1	99.00	100.00	1.00	0.06	0.30	0.075			0.004
				135.50-135.70 Feldspar Porphyry: phenocrysts <5 mm	44335	1	100.00	101.00	1.00	0.01	0.20	0.054			0.002
					44336	1	101.00	102.00	1.00	0.03	0.20	0.058			0.001
					44337	1	102.00	103.00	1.00	0.01	0.10	0.065			0.000
					44338	1	103.00	104.00	1.00	0.01	0.10	0.052			0.001
					44339	1	104.00	105.00	1.00	0.01	0.60	0.118			0.002
					44340	1	105.00	105.50	0.50	0.01	0.10	0.055			0.001
					44342	1	105.50	106.23	0.73	0.06	0.40	0.103			0.001
					44343	3	106.23	107.00	0.77	0.06	0.70	0.101			0.002
					44344	3	107.00	108.00	1.00	0.07	0.90	0.089			0.003
					44345	3	108.00	109.00	1.00	0.01	0.70	0.061			0.003
					44346	3	109.00	110.00	1.00	0.07	0.90	0.115			0.003
					44347	3	110.00	111.00	1.00	0.04	0.60	0.070			0.003
					44348	3	111.00	112.00	1.00	0.09	1.20	0.162			0.005

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					44349	3	112.00	113.00	1.00	0.08	1.50	0.251			0.007
					44352	3	113.00	114.00	1.00	0.07	0.70	0.077			0.003
					44353	3	114.00	115.00	1.00	0.09	0.90	0.109			0.002
					44354	3	115.00	116.00	1.00	0.01	0.70	0.066			0.002
					44355	3	116.00	117.00	1.00	0.41	1.10	0.105			0.004
138.80	146.75	FP	FP	as above: moderate pink alteration	44356	3	117.00	118.00	1.00	0.12	0.80	0.075			0.003
					44357	3	118.00	119.00	1.00	0.13	0.60	0.058			0.003
					44358	3	119.00	120.00	1.00	0.11	0.80	0.087			0.002
				140.35-140.85 Cgl	44359	3	120.00	121.00	1.00	0.04	0.50	0.071			0.001
					44360	3	121.00	122.00	1.00	0.07	0.80	0.101			0.001
					44362	3	122.00	123.00	1.00	0.01	0.50	0.132			0.003
					44363	3	123.00	124.00	1.00	0.01	0.60	0.073			0.004
					44364	3	124.00	125.00	1.00	0.03	0.90	0.086			0.002
					44365	2	125.00	126.00	1.00	0.01	0.40	0.025			0.001
					44366	2	126.00	127.00	1.00	0.06	0.40	0.073			0.002
					44367	2	127.00	128.00	1.00	0.11	0.50	0.112			0.002
					44368	2	128.00	129.00	1.00	0.01	0.80	0.092			0.002
146.75	150.00	CGL	CGL	as above:	44369	2	129.00	130.00	1.00	0.01	0.70	0.096			0.003
				147.80-147.94 FP	44372	2	130.00	131.00	1.00	0.10	0.70	0.145			0.003
				148.70-149.40 FP contacts at 50, 40 and 20 CA	44373	2	131.00	132.00	1.00	0.10	0.60	0.128			0.002
				149.40-149.70 50% quartz veining at 40 CA; strong disseminated pyrite	44374	2	132.00	133.00	1.00	0.01	0.30	0.049			0.002
					44375	2	133.00	134.00	1.00	0.07	0.40	0.077			0.002
					44376	2	134.00	135.00	1.00	0.05	0.50	0.112			0.003
					44377	2	135.00	136.00	1.00	0.01	0.30	0.102			0.002
					44378	2	136.00	137.00	1.00	0.05	0.60	0.101			0.005
					44379	2	137.00	138.00	1.00	0.09	0.60	0.128			0.002
					44380	2	138.00	138.80	0.80	0.08	0.70	0.143			0.006
					44382	1	138.80	140.00	1.20	0.05	0.30	0.028			0.001
					44383	1	140.00	141.00	1.00	0.07	0.40	0.102			0.004
					44384	1	141.00	142.00	1.00	0.06	0.40	0.083			0.001
150.00	171.15	FP	FP	as above: contact at 40 and 20 CA	44385	1	142.00	143.00	1.00	0.04	0.20	0.029			0.002
				150.00-161.00 strong hematite alteration; moderate red alteration	44386	1	143.00	144.00	1.00	0.01	0.20	0.051			0.001
					44387	1	144.00	145.00	1.00	0.05	0.20	0.037			0.002
				165.05-165.65 sheared strongly at 50 CA; 50% quartz veining with strongly disseminated pyrite	44388	1	145.00	146.00	1.00	0.04	0.20	0.024			0.001
					44389	1	146.00	146.75	0.75	0.03	0.10	0.012			0.001
					44392	1	146.75	147.50	0.75	0.01	0.40	0.050			0.001
					44393	1	147.50	148.00	0.50	0.01	0.10	0.020			0.001
					44394	3	148.00	149.00	1.00	0.01	0.20	0.052			0.001
				170.30- 3 cm quartz vein at 20-30 CA	44395	3	149.00	150.00	1.00	0.21	1.00	0.083			0.002
					44396	1	150.00	151.00	1.00	0.02	0.70	0.157			0.001
171.15	179.90	Greywacke	GWE	as above: very uniform, massive; medium grey, fine grained	44397	1	151.00	152.00	1.00	0.08	0.10	0.084			0.000
					44398	1	152.00	153.00	1.00	0.01	0.20	0.074			0.001

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					44399	1	153.00	154.00	1.00	0.01	0.60	0.153			0.003
179.90	180.70	FP	FP	as above: medium grey; 2-3% disseminated pyrite;	44400	1	154.00	155.00	1.00	0.11	0.40	0.093			0.001
				quartz vein 1 cm at 50 CA; contact at 30 CA	44402	1	155.00	156.00	1.00	0.04	0.70	0.072			0.001
					44403	1	156.00	157.00	1.00	0.02	1.00	0.094			0.000
180.70	182.40	Greywacke	GWE	as above:	44404	1	157.00	158.00	1.00	0.03	0.70	0.047			0.000
					44405	1	158.00	159.00	1.00	0.04	0.50	0.047			0.000
					44406	1	159.00	160.00	1.00	0.05	0.70	0.078			0.002
182.40	191.20	FP	FP	as above:	44407	1	160.00	161.00	1.00	0.01	0.80	0.089			0.001
					44408	1	161.00	162.00	1.00	0.05	0.80	0.089			0.000
					44409	1	162.00	163.00	1.00	0.03	1.00	0.113			0.000
				184.3 1 cm quartz vein at 50 CA	44412	1	163.00	164.00	1.00	0.04	0.70	0.089			0.001
					44413	1	164.00	165.00	1.00	0.10	2.40	0.042			0.001
				186.3 3 cm quartz vein at 50 CA	44414	3	165.00	166.00	1.00	0.32	4.20	0.023			0.005
					44415	1	166.00	167.00	1.00	0.03	1.40	0.111			0.001
191.20	289.65	Diabase	DIA	as above: fine to medium grained, contact at 30 CA	44416	1	167.00	168.00	1.00	0.07	1.20	0.049			0.005
					44417	1	168.00	169.00	1.00	0.05	1.70	0.107			0.001
289.65	305.40	Greywacke	GWE	as above: 1-2% disseminated pyrite, traces	44418	1	169.00	170.00	1.00	0.05	1.50	0.104			0.007
				chalcopyrite	44419	1	170.00	171.15	1.15	0.01	0.70	0.058			0.012
					44420	1	171.15	172.00	0.85	0.08	0.80	0.091			0.001
					44422	1	172.00	173.00	1.00	0.01	0.10				
				299.0- traces chalcopyrite	44423	1	173.00	174.00	1.00	0.01	0.20				
					44424	1	174.00	175.00	1.00	0.01	0.40				
					44425	1	175.00	176.00	1.00	0.01	0.30				
305.40	306.00	FP	FP	as above: contact at 80 CA; 10% quartz veining at 20 CA	44426	1	176.00	177.00	1.00	0.01	0.20				
					44427	1	177.00	178.00	1.00	0.01	0.10				
306.00	332.60	Greywacke	GWE	as above:	44428	1	178.00	179.00	1.00	0.02	0.10				
					44429	1	179.00	179.90	0.90	0.01	0.10				
				308.0-308.4 FP	44432	1	179.90	181.00	1.10	0.01	0.10				
					44433	1	181.00	182.00	1.00	0.01	0.20				
				331.7 2 cm quartz vein at 40 CA	44434	2	182.00	183.00	1.00	0.01	0.30				
				331-332.6 3-5% disseminated pyrite	44435	2	183.00	184.00	1.00	0.01	0.10				
					44436	2	184.00	185.00	1.00	0.01	0.30				
					44437	1	185.00	186.00	1.00	0.01	0.30				
332.60	337.40	CGL	CGL	as above:	44438	1	186.00	187.00	1.00	0.01	0.30				
					44439	1	187.00	188.00	1.00	0.01	0.30				
					44440	1	188.00	189.00	1.00	0.01	0.70				
337.40	338.40	FP	FP	as above:	44442	1	189.00	190.00	1.00	0.35	1.20				
					44443	2	190.00	191.20	1.20	1.22	2.80				
338.40	349.00	CGL	CGL	as above:	44444	2	289.65	290.00	0.35	0.01	0.20	0.008			
					44445	2	290.00	291.00	1.00	0.01	0.40	0.019			
					44446	1	291.00	292.00	1.00	0.01	0.30	0.017			
					44447	1	292.00	293.00	1.00	0.01	0.50	0.014			

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					44448	1	293.00	294.00	1.00	0.01	0.20	0.012			
					44449	1	294.00	295.00	1.00	0.01	0.40	0.034			
					44452	1	295.00	296.00	1.00	0.01	0.20	0.024			
					44453	1	296.00	297.00	1.00	0.02	0.30	0.015			
				343.30-344.70 3-5% disseminated pyrite	44454	1	297.00	298.00	1.00	0.03	0.40	0.031			
					44455	1	298.00	299.00	1.00	0.01	0.40	0.023			
					44456	1	299.00	300.00	1.00	0.01	0.20	0.039			
					44457	1	300.00	301.00	1.00	0.01	0.30	0.010			
					44458	1	301.00	302.00	1.00	0.01	0.10	0.053			
					44459	1	302.00	303.00	1.00	0.01	0.40	0.043			
					44460	1	303.00	304.00	1.00	0.01	0.50	0.015			
349.00	406.00	Greywacke	GWE	as above: disseminated magnetite	44462	1	304.00	305.00	1.00	0.01	0.10	0.015			
					44463	1	305.00	305.40	0.40	0.01	0.30	0.016			
				357.1 trace chalcopyrite	44464	1	305.40	306.00	0.60	0.01	0.20	0.023			
				361.00-369.00 pebble band with 2-3% disseminated pyrite	44465	1	306.00	307.00	1.00	0.01	0.20	0.021			
					44466	1	307.00	308.00	1.00	0.01	0.30	0.041			
					44467	1	308.00	309.00	1.00	0.01	0.10	0.019			
					44468	1	309.00	310.00	1.00	0.01	0.20	0.018			
					44469	1	310.00	311.00	1.00	0.01	0.20	0.017			
					44472	3	331.00	332.00	1.00	0.13	0.20				
					44473	4	332.00	332.60	0.60	0.01	0.50				
					44474	1	332.60	333.00	0.40	0.01	0.20				
					44475	1	333.00	334.00	1.00	0.01	0.10				
					44476	1	334.00	335.00	1.00	0.01	0.20				
					44477	1	335.00	336.00	1.00	0.01	0.30				
					44478	1	336.00	337.00	1.00	0.01	0.30				
					44479	1	337.00	337.84	0.84	0.01	0.10				
406.00	406.50	FP	FP	as above: contact at 20 CA	44480	1	337.84	338.40	0.56	0.01	0.40				
					44482	1	338.40	339.00	0.60	0.01	0.10				
					44483	1	339.00	340.00	1.00	0.01	0.10				
					44484	1	340.00	341.00	1.00	0.04	0.10				
					44485	1	341.00	342.00	1.00	0.01	0.40				
					44486	1	342.00	343.00	1.00	0.01	0.10				
					44487	5	343.00	344.00	1.00	1.12	0.40				
					44488	5	344.00	345.00	1.00	0.08	0.30				
406.50	421.50	Greywacke	GWE	as above: non-magnetic	44489	3	345.00	346.00	1.00	0.01	0.10				
					44492	2	346.00	347.00	1.00	0.01	0.10				
					44493	2	347.00	348.00	1.00	0.01	0.20				
					44494	2	348.00	349.00	1.00	0.01	0.10				
421.50	456.00	Diabase	DIA	as above: contact at 40 CA	44495	1	357.00	358.00	1.00	0.01	0.10				
					44496	1	358.00	359.00	1.00	0.02	0.10				
				421.0-421.5 pale green, strongly sheared at 40 CA	44497	1	359.00	360.00	1.00	0.01	0.10				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
				483.1 2 cm quartz vein at 50 CA	44498	1	360.00	361.00	1.00	0.02	0.10				
				484.54 1 cm quartz vein at 50 CA; trace chalcopyrite	44499	1	361.00	362.00	1.00	0.07	0.10				
					44500	1	362.00	363.00	1.00	0.03	0.20				
456.00	495.00	Greywacke	GWE	as above: contact at 40 CA	44502	1	363.00	364.00	1.00	0.01	0.20				
					44503	1	364.00	365.00	1.00	0.01	0.30				
495.00	498.00	CGL	CGL	as above: contact at 40 CA	44504	1	365.00	366.00	1.00	0.01	0.70				
					44505	1	366.00	367.00	1.00	0.01	0.50				
					44506	1	367.00	368.00	1.00	0.01	0.30				
					44507	1	368.00	369.00	1.00	0.01	0.10				
				EOH	44508		483.00	484.00	1.00	0.01	0.20				
					44509		484.00	485.00	1.00	0.04	0.10				
				core stored at Matachewan											
Downhole Tests:															
	Depth	AZ	DIP												
	51	333.6	-48.8												
	102	336.4	-48.5												
	150	336.7	-48.7												
	201	338.7	-48.6												
	250	339.2	-48.8												
	300	343.3	-48.6												
	351	343.7	-48.5												
	402	343.8	-48.6												
	501	347.1	-48.4												

Opawica Explorations Inc.

Matachewan
 DDH#: OPW-07-018
 Az and Dip: 330/-50
 E.O.H: 300 m

GRID LOCATION: Powell Twp., Ontario
 GRID: OPW: 6W 13+00S
 UTM, type: 0521948E, 5311401N: Nad: 83 Zone: 17
 Elev.:

Claim: L373507
 Drill Company: Downing: NQ Core
 Logged by: Fred Sharpley
 Start: August 09, 2007; End: August 11, 2007

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
0.00	2.60		OVB												
2.60	24.10	Siltstone	SILT	light grey, very fine grained, weakly banded at 40 CA 1-2% finely disseminated pyrite	44510	1	12.00	13.00	1.00	0.01	0.10				
					44511		13.00	14.00	1.00	0.05	0.30				
					44512		14.00	15.00	1.00	0.05	0.30				
					44513	1	21.00	22.00	1.00	0.01	0.20				
24.10	28.20	FP	FP	medium grey, fine grained groundmass, with coarse grained <1 cm pink phenocrysts; contact at 40-50 CA	44514	1	22.00	23.00	1.00	0.04	0.50				
					44515	1	23.00	24.10	1.10	0.01	0.10				
					44516	1	24.10	25.00	0.90	0.01	0.10				
28.20	39.90	Siltstone	SILT	as above: 1-2% disseminated pyrite	44517	1	25.00	26.00	1.00	0.01	0.10				
					44518	1	26.00	27.00	1.00	0.01	0.20				
					44520	1	27.00	28.20	1.20	0.01	0.20				
					44521	1	28.20	29.00	0.80	0.01	0.20				
					44522	1	29.00	30.00	1.00	0.01	0.60				
					44523	1	30.00	31.00	1.00	0.01	0.20				
					44524	1	31.00	32.00	1.00	0.01	0.10				
					44525	1	32.00	33.00	1.00	0.01	0.20				
39.90	41.60	Argillite	ARG	black, fine grained bedded at 30 CA	44526	1	50.00	50.80	0.80	0.01	0.20				
					44527	1	50.80	51.50	0.70	0.01	0.10				
41.60	50.80	Siltstone	SILT	as above: 1-2% disseminated pyrite	44530	1	51.50	52.00	0.50	0.01	0.20				
					44531	1	52.00	53.00	1.00	0.01	0.10				
					44532	1	53.00	54.00	1.00	0.01	0.10				
					44533	1	54.00	55.00	1.00	0.03	0.10				
50.80	61.30	FP	FP	as above: contact at 30 CA; 1-2 % disseminated py	44534	1	55.00	56.00	1.00	0.01	0.10				
					44535	1	56.00	57.00	1.00	0.01	0.10				
					44536	1	57.00	58.00	1.00	0.01	0.20				
					44537	1	58.00	59.00	1.00	0.02	0.20				
					44538	1	59.00	60.00	1.00	0.01	0.20				
					44540	1	60.00	61.00	1.00	0.01	0.10				
					44541	1	61.00	61.30	0.30	0.01	0.30				
					44542	2	61.30	62.00	0.70	0.03	0.20				
61.30	73.30	Siltstone	SILT	as above: 1-2% disseminated pyrite	44543	2	62.00	63.00	1.00	0.01	0.10				
					44544	2	63.00	64.00	1.00	0.01	0.20				
					44545	2	64.00	65.00	1.00	0.02	0.30				
					44546	2	65.00	66.00	1.00	0.01	0.40				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					44547	2	66.00	67.00	1.00	0.01	0.30				
					44550	2	67.00	68.00	1.00	0.01	0.10				
					44551	2	68.00	69.00	1.00	0.01	0.20				
					44552	2	71.00	72.00	1.00	0.01	0.10				
					44553	2	72.00	73.30	1.30	0.07	0.30				
					44554	3	73.30	73.60	0.30	0.15	0.40				
73.30	73.60	Fault Zone	FZ	light grey, sericitized strongly; strongly sheared at 60CA	44555	2	73.60	74.00	0.40	0.01	0.10				
				1-2% disseminated pyrite	44556	2	74.00	75.00	1.00	0.01	0.10				
					44557	2	75.00	76.00	1.00	0.01	0.10				
73.60	113.30	CGL	CGL	light grey, cobbles of siltstone, rounded. <5 cm	44558	2	76.00	77.00	1.00	0.01	0.10				
					44560	1	110.00	111.00	1.00	0.01	0.10				
					44561	1	111.00	112.00	1.00	0.02	0.10				
					44562	1	112.00	113.30	1.30	0.03	0.20				
113.30	155.27	Siltstone	SILT	as above: bedded at 50 CA;	44563	1	113.30	114.00	0.70	0.01	0.10				
					44564	1	114.00	115.00	1.00	0.05	0.20				
				110.0-120.0 1-3% disseminated pyrite	44565	1	115.00	116.00	1.00	0.01	0.10				
					44566	1	116.00	117.00	1.00	0.01	0.10				
					44567	1	117.00	118.00	1.00	0.01	0.10				
					44570	1	118.00	119.00	1.00	0.01	0.10				
					44571	1	119.00	120.00	1.00	0.01	0.30				
					44572	2	132.00	133.00	1.00	0.01	0.10				
				132.0-140.0 1-3% disseminated pyrite	44573	2	133.00	134.00	1.00	0.02	0.10				
					44574	2	134.00	135.00	1.00	0.01	0.10				
					44575	2	135.00	136.00	1.00	0.01	0.10				
					44576	2	136.00	137.00	1.00	0.01	0.10				
					44577	2	137.00	138.00	1.00	0.01	0.10				
					44578	2	138.00	139.00	1.00	0.01	0.10				
					44580	2	139.00	140.00	1.00	0.01	0.10				
					44581	2	152.00	153.00	1.00	0.01	0.10				
					44582	2	153.00	154.00	1.00	0.05	0.10				
					44583	2	154.00	155.27	1.27	0.02	0.10				
155.27	245.00	CGL	CGL	as above:	44584	2	155.27	156.00	0.73	0.05	0.10				
					44585	2	156.00	157.00	1.00	0.01	0.10				
				152.0-173.0 1-3% disseminated pyrite	44586	2	157.00	158.00	1.00	0.06	0.10				
					44587	2	158.00	159.00	1.00	0.06	0.30				
					44590	2	159.00	160.00	1.00	0.04	0.10				
					44591	2	160.00	161.00	1.00	0.04	0.10				
					44592	2	161.00	162.00	1.00	0.04	0.10				
					44593	2	162.00	163.00	1.00	0.03	0.20				
					44594	2	163.00	164.00	1.00	0.03	0.10				
					44595	2	164.00	165.00	1.00	0.06	0.10				
					44596	2	165.00	166.00	1.00	0.04	0.10				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					44597	2	166.00	167.00	1.00	0.04	0.10				
					44598	2	167.00	168.00	1.00	0.20	0.70				
					44600	2	168.00	169.00	1.00	0.07	0.10				
					44601	2	169.00	170.00	1.00	0.03	0.20				
					44602	2	170.00	171.00	1.00	0.03	0.10				
					44603	2	171.00	172.00	1.00	0.05	0.10				
					44604	2	172.00	173.00	1.00	0.05	0.20				
					44605	2	173.00	174.00	1.00	0.04	0.10				
					44606	2	174.00	175.00	1.00	0.08	0.40				
					44607	2	175.00	176.00	1.00	0.02	0.10				
					44610	2	176.00	177.00	1.00	0.04	0.30				
					44611	2	187.00	188.00	1.00	0.01	0.10				
					44612	2	188.00	189.00	1.00	0.02	0.60				
					44613	2	189.00	190.00	1.00	0.02	0.60				
					44614	2	190.00	191.00	1.00	0.01	0.10				
					44615	2	191.00	192.00	1.00	0.01	0.10				
					44616	2	192.00	193.00	1.00	0.18	1.60				
					44617	2	193.00	194.00	1.00	0.34	2.30				
					44618	2	194.00	195.00	1.00	0.01	0.20				
					44619	2	195.00	196.00	1.00	0.03	0.40				
					44621	2	196.00	197.00	1.00	0.01	0.20				
				188.0-199.0 weak sericite alteration with weak disseminated pyrite; 1-2% pyrite	44622	2	197.00	198.00	1.00	0.03	0.10				
					44623	2	198.00	199.00	1.00	0.06	0.40				
					44624	1	199.00	200.00	1.00	0.03	0.20				
					44625	1	200.00	201.00	1.00	0.05	0.40				
					44626	1	201.00	202.00	1.00	0.03	0.40				
					44627	1	202.00	203.00	1.00	0.12	1.00				
					44628	1	203.00	204.00	1.00	0.01	0.20				
					44631	1	204.00	205.00	1.00	0.02	0.30				
				210.70-211.0 40% quartz veining at 50 CA	44632	1	205.00	206.00	1.00	0.02	0.30				
					44633	1	206.00	207.00	1.00	0.01	0.10				
					37365		210.00	211.00	1.00	1.15					
					37366		211.00	212.00	1.00	0.10					
				225.2-242.0 pebble greywacke	44634	3	237.00	238.00	1.00	0.01	0.40				
					44635	3	238.00	239.00	1.00	0.06	1.30				
				237.5-237.7 carbonated zone with 2-3% disseminated pyrite	44636	2	281.30	282.00	0.70	0.02	0.20				
					44637	2	282.00	283.00	1.00	0.01	0.20				
					44638	2	283.00	284.00	1.00	0.01	0.10				
245.00	246.40	Mafic Dike	MAF	dark green, fine grained, massive, uniform; contact at 20 and 60 CA	44640	2	284.00	285.00	1.00	0.01	0.30				
					44641	2	285.00	286.00	1.00	0.01	0.20				
					44642	2	286.00	287.00	1.00	0.01	0.50				
246.40	255.20	CGL	CGL	as above:	44643	2	287.00	288.00	1.00	0.02	0.50				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
255.20	260.60	Siltstone	SILT	as above:	44644	2	288.00	289.00	1.00	0.02	0.70				
					44645	2	289.00	290.00	1.00	0.01	0.30				
					44646	2	290.00	291.00	1.00	0.31	0.30				
260.60	278.80	CGL	CGL	as above:	44647	2	291.00	292.00	1.00	0.01	0.20				
					44650	2	292.00	293.00	1.00	0.18	0.60				
278.80	281.30	Mafic Dike:	MAF	as above: contact at 60 CA	44651	2	293.00	294.00	1.00	0.23	0.50				
					44652	2	294.00	295.00	1.00	0.01	0.30				
281.30	296.10	CGL	CGL	as above: 2-3% disseminated pyrite	44653	2	295.00	296.10	1.10	0.14	0.70				
					44654		296.10	296.40	0.30	0.01	0.20				
					44655	2	296.40	297.00	0.60	0.01	0.30				
296.10	296.40	Mafic Dike	MAF	as above	44656	2	297.00	297.70	0.70	0.01	0.30				
					44657		297.70	298.40	0.70	0.01	0.40				
296.40	297.70	CGL	CGL	as above:	44658	2	298.40	299.00	0.60	0.01	0.20				
					44660	2	299.00	300.00	1.00	0.01	0.30				
297.70	298.40	Mafic Dike	MAF	as above											
298.40	300.00	CGL	CGL	as above:											
				EOH											
				core stored in Matachewan											
Downhole Tests:															
	Depth	AZ	DIP												
	54	331.7	-48												
	105	332.9	-47.6												
	153	333.6	-47.1												
	204	334.4	-46.9												
	255	335.6	-46.1												
	300	338.4	-45.7												

Opawica Explorations Inc.

Matachewan
DDH#: OPW-07-019
Az and Dip: 150/-65
E.O.H: 600 m

GRID LOCATION: Powell Twp., Ontario
GRID: OPW: 850W 5+00N
UTM, type: 0520804E, 5312849N: Nad: 83 Zone: 17
Elev.:

Claim: 374240
Drill Company: Downing: NQ Core
Logged by: Fred Sharpley
Start: August 10, 2007; End: August 22, 2007

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
0.00	1.10		OVB												
					44188	2	43.00	44.00	1.00	0.01	0.30				
1.10	43.00	Diabase	DIA	medium grey, fine grained massive uniform; sharp contact at 20 CA	44189	2	44.00	45.00	1.00	0.01	0.40				
					44190	2	45.00	46.00	1.00	0.01	0.10				
					44191	2	46.00	47.00	1.00	0.01	0.40				
43.00	51.80	Greywacke	GWE	medium grey, fine grained; weakly altered, bleached locally with 1-2% disseminated pyrite	44192	2	47.00	48.00	1.00	0.02	1.60				
					44193	2	48.00	49.00	1.00	0.01	1.00				
					44194	2	49.00	50.00	1.00	0.01	0.50				
51.80	52.80	FZ	FZ	strongly sheared at 60 CA; strongly bleached; very hard strongly silicified; <1% pyrite, trace of chalcopyrite	44195	2	50.00	51.00	1.00	0.01	0.10				
					44197	2	51.00	51.80	0.80	0.01	0.30				
					44198	2	51.80	52.80	1.00	0.02	1.30				
52.80	58.56	Greywacke	GWE	as above: weakly altered; 1% pyrite	44199	2	52.80	54.00	1.20	0.01	0.40				
					44200	2	54.00	55.00	1.00	0.01	0.50				
					44201	2	55.00	56.00	1.00	0.01	0.50				
					44202	2	56.00	57.00	1.00	0.01	0.20				
					44203	2	57.00	58.00	1.00	0.01	0.30				
					44204	2	58.00	58.56	0.56	0.01	0.50				
					44207	2	58.56	59.00	0.44	0.01	2.80				
					44208	2	59.00	60.00	1.00	0.01	2.10				
					44209	2	60.00	61.00	1.00	0.01	1.80				
58.56	64.75	Argillite	ARG	black color, very fine grained, banded at 40 CA; 1-2% disseminated pyrite, trace of chalcopyrite	44210	2	61.00	62.00	1.00	0.03	1.90				
					44211	2	62.00	63.00	1.00	0.01	1.20				
					44212	2	63.00	64.00	1.00	0.01	0.90				
					44213	2	64.00	64.75	0.75	0.01	0.90				
					44214	2	64.75	65.00	0.25	0.01	0.40				
					44215	2	65.00	66.00	1.00	0.01	0.20				
					44217	1	66.00	67.00	1.00	0.01	0.20				
					44218	1	67.00	68.00	1.00	0.01	0.20				
64.75	75.70	Greywacke	GWE	as above: weak bleach alteration in patches; 1-2% disseminated pyrite	44219	1	68.00	69.00	1.00	0.01	0.30				
					44220	1	69.00	70.00	1.00	0.01	0.40				
					44221	1	70.00	71.00	1.00	0.01	0.40				
					44222	1	71.00	72.00	1.00	0.01	0.10				
					44223	1	72.00	73.00	1.00	0.01	0.10				
					44224	1	73.00	74.00	1.00	0.01	0.10				
					44227	1	74.00	75.00	1.00	0.01	0.10				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					44228	1	75.00	75.70	0.70	0.01	1.20				
					44229	1	75.70	77.00	1.30	0.01	0.90				
75.70	102.40	FP	FP	pale grey, fine grained groundmass, porphyritic, 1-2mm white feldspar phenocrysts; 1% disseminated pyrite;	44230	1	77.00	78.00	1.00	0.01	0.20				
				contact at 60 CA	44231	1	78.00	79.00	1.00	0.01	0.50				
					44232	1	79.00	80.00	1.00	0.01	0.10				
					44233	1	80.00	81.00	1.00	0.01	0.10				
				78.4-79.0 quartz vein at 20 CA	44234	1	81.00	82.00	1.00	0.01	0.20				
					44235	1	82.00	83.00	1.00	0.01	0.40				
				82.8 1 cm quartz vein at 40 CA	44237	1	83.00	84.00	1.00	0.01	0.50				
					44238	1	84.00	85.00	1.00	0.01	0.20				
				86.15 1cm quartz vein at 70 CA	44239	1	85.00	86.00	1.00	0.01	0.10				
					44240	1	86.00	87.00	1.00	0.01	0.20				
				92.5 1 cm quartz vein at 50 CA	44241	1	87.00	88.00	1.00	0.01	0.20				
					44242	1	88.00	89.00	1.00	0.01	0.20				
				93.15 1 cm quartz vein at 50 CA	44243	1	89.00	90.00	1.00	0.01	0.70				
					44244	1	90.00	91.00	1.00	0.01	0.20				
					44247	1	91.00	92.00	1.00	0.01	0.40				
					44248	1	92.00	93.00	1.00	0.01	0.10				
					44249	1	93.00	94.00	1.00	0.01	0.10				
				96.1 2 cm quartz vein at 60 CA	44250	1	94.00	95.00	1.00	0.01	0.20				
					44251	1	95.00	96.00	1.00	0.01	0.10				
					44252	1	96.00	97.00	1.00	0.01	0.20				
					44253	1	97.00	98.00	1.00	0.01	0.10				
					44254	1	98.00	99.00	1.00	0.01	0.10				
					44255	1	99.00	100.00	1.00	0.01	0.20				
					44257	1	100.00	101.00	1.00	0.01	0.20				
102.40	102.70	FZ	FZ	strongly sheared at 70 CA;	44258	1	101.00	102.00	1.00	0.01	0.40				
					44259	1	102.00	102.40	0.40	0.01	0.10				
102.70	128.87	Diabase	DIA	as above:	44260		102.40	102.70	0.30	0.01	0.10				
					36900	1	393.00	393.50	0.50	0.08	0.20				
128.87	130.00	FZ	FZ	strongly sheared at 50 CA; sericite-chlorite alteration.	36901	1	399.00	400.00	1.00	0.01	0.10				
					36902	1	400.00	401.00	1.00	0.01	0.10				
130.00	143.30	Siltstone	SILT	light grey, very fine grained, weakly banded at 50 CA;	36903	1	401.00	402.00	1.00	0.01	0.10				
					36906	1	402.00	403.00	1.00	0.01	0.30				
143.30	150.30	Argillite	ARG	as above:	36907	1	403.00	404.00	1.00	0.01	0.10				
					36908	1	404.00	405.00	1.00	0.01	0.10				
150.30	163.10	Greywacke	GWE	as above:	36909	1	405.00	406.00	1.00	0.01	0.10				
					36910	1	406.00	407.00	1.00	0.01	0.10				
				152.5 1 cm quartz vein at 30 CA	36911	1	407.00	408.00	1.00	0.01	0.10				
					36912	1	408.00	409.00	1.00	0.01	0.20				
163.10	357.90	Diabase	DIA	as above:	36913	1	409.00	410.00	1.00	0.01	0.10				
					36914	1	410.00	411.00	1.00	0.01	0.10				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
357.90	358.40	Fault Zone	FZ	strongly sheared chlorite hematite breccia at 50-70 CA	36916	1	411.00	412.00	1.00	0.01	0.10				
					36917	1	412.00	413.00	1.00	0.01	0.10				
358.40	369.95	Diabase	DIA	as above:	36918	1	413.00	413.80	0.80	0.01	0.10				
					36919	1	413.80	414.70	0.90	0.01	0.10				
369.95	380.10	Greywacke	GWE	as above:	36920	1	414.70	415.50	0.80	0.01	0.10				
				369.95-380.1 weak to moderate hematite alteration	36921	1	415.50	416.00	0.50	0.01	0.10				
380.10	381.65	Diabase	DIA	as above: contact at 50 CA	36922	1	416.00	417.00	1.00	0.01	0.10				
					36923	1	417.00	418.00	1.00	0.01	0.10				
381.65	392.40	Greywacke	GWE	as above:	36926	1	418.00	419.00	1.00	0.01	0.10				
				386.0-398.9 weak to moderate hematite alteration	36927	1	419.00	420.00	1.00	0.01	0.10				
392.40	393.00	Diabase	DIA	as above:	36928	1	420.00	421.00	1.00	0.01	0.10				
					36929	1	421.00	422.00	1.00	0.04	0.10				
393.00	413.80	Greywacke	GWE	386.0-398.9 weak to moderate hematite alteration;	36930	1	422.00	423.00	1.00	0.06	0.10				
				similar to above; silicified, very fine disseminated	36931	1	423.00	424.00	1.00	0.34	0.10				
				pyrite.	36932	1	424.00	425.00	1.00	0.01	0.10				
					36933	1	425.00	426.00	1.00	0.07	0.10				
				401.80-403.0 core broken up, numerous slips at 60 CA	36934	1	426.00	427.00	1.00	0.01	0.10				
					36936	1	427.00	428.00	1.00	0.04	0.10				
				410.60-411.00 Lamprophyre Dike: contact at 60 CA	36937	1	428.00	429.00	1.00	0.01	0.10				
					36938	1	429.00	430.00	1.00	0.02	0.10				
					36939	1	430.00	431.00	1.00	0.01	0.10				
					36940	1	431.00	432.00	1.00	0.13	0.10				
					36941	1	432.00	433.00	1.00	0.01	0.10				
413.80	414.70	TALC	TALC	Ultramafic Dike: medium black, altered to talc-chlorite;	36942	1	433.00	434.00	1.00	0.13	0.10				
				sharp contact at 60 CA;	36943	1	434.00	435.00	1.00	0.17	0.10				
					36946	1	435.00	436.00	1.00	0.01	0.10				
414.70	434.10	Greywacke	GWE	Hematite Alt: moderate to strong hematite alteration;	36947	1	436.00	437.00	1.00	0.96	0.10				
				similar to above; silicified, very fine disseminated	36948	1	437.00	438.00	1.00	0.34	0.10				
				pyrite; strongly fractured; pyrite	36949	1	438.00	439.00	1.00	0.28	0.10				
					36950	1	439.00	440.00	1.00	0.71	0.30				
					36951	15	440.00	441.00	1.00	2.21	0.70				
434.10	435.00	LAM	LAM	as above: contact at 50 CA	36952	8	441.00	442.00	1.00	0.89	0.30				
					36953	5	442.00	443.00	1.00	0.26	0.20				
					36954	15	443.00	444.00	1.00	1.24	0.40				
435.00	455.50	Greywacke	CKZ	as above: contact at 50 CA; Strong Hematite Alteration	36956	15	444.00	445.00	1.00	0.24	0.60				
					36957	5	445.00	446.00	1.00	0.10	0.20				
					36958	5	446.00	447.00	1.00	0.39	0.20				
				439.84 sheared quartz carbonate vein, 2 cm, at 70CA	36959	5	447.00	448.00	1.00	1.41	0.50				
				439.84-445.12 10-15% very finely disseminated pyrite	36960	5	448.00	449.00	1.00	1.11	0.30				
					36961	5	449.00	450.00	1.00	0.77	0.30				
				435.00-464.6 Strong Alteration Zone: hematite-silicified;	36962	5	450.00	451.00	1.00	0.09	0.30				
				brecciated in situ; 5-15% finely disseminate pyrite	36963	5	451.00	452.00	1.00	0.01	0.30				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					36966	5	452.00	453.00	1.00	0.07	0.30				
					36967	5	453.00	454.00	1.00	0.04	0.30				
					36968	5	454.00	455.00	1.00	0.12	0.70				
					36969	5	455.00	455.50	0.50	0.32	1.20				
					36970		455.50	455.90	0.40	0.05	0.70				
455.50	455.90	LAM	LAM	as above: contact at 60 CA	36971	5	455.90	457.00	1.10	0.05	0.30				
					36972	5	457.00	458.10	1.10	0.07	0.10				
455.90	458.10	Greywacke	CKZ	Hematite Alt: moderate to strong hematite alteration; fine disseminated pyrite	36973		458.10	459.00	0.90	0.01	0.20				
					36974		459.00	459.64	0.64	0.03	0.20				
458.10	459.64	LAM	LAM	as above: contact at 70 CA	36976	5	459.64	460.10	0.46	0.02	0.40				
					36977		460.10	460.95	0.85	0.01	0.50				
459.64	460.10	Fault Zone	FZ	strongly sheared quartz carbonate breccia at 40 CA	36978	3	460.95	462.00	1.05	0.18	0.30				
					36979	3	462.00	463.00	1.00	0.17	0.10				
460.10	460.95	Lam	LAM	as above: contact at 50 CA	36980	3	463.00	464.00	1.00	0.24	0.30				
					36981	3	464.00	464.60	0.60	0.22	0.20				
460.95	464.60	Greywacke	CKZ	as above:	36982	2	464.60	465.00	0.40	0.04	0.20				
					36983	2	465.00	466.00	1.00	0.05	0.20				
464.60	487.20	Greywacke	GWE	medium grey, fine grained, weakly foliated at 40 CA	36986	2	466.00	467.00	1.00	0.18	0.30				
					36987	2	467.00	468.00	1.00	0.07	0.20				
					36988	2	468.00	469.00	1.00	0.01	0.20				
					36989	2	469.00	470.00	1.00	0.01	0.30				
				464.60-467.0 weak hematite-silicified, crackle breccia 1-3% very finely disseminated pyrite	36990	2	470.00	471.00	1.00	0.01	0.20				
					36991	2	471.00	472.00	1.00	0.09	0.30				
					36992	2	472.00	473.00	1.00	0.05	0.10				
					36993	2	473.00	474.00	1.00	0.02	0.10				
					36994	2	474.00	475.00	1.00	0.04	0.10				
					36996	3	475.00	476.00	1.00	0.05	0.10				
					36997	3	476.00	477.00	1.00	0.11	0.20				
					36998	3	477.00	478.00	1.00	0.18	0.20				
				475.00-478.70 weak hematite alteration; 1-3% py	36999	3	478.00	479.00	1.00	0.14	0.10				
					37000	1	479.00	480.00	1.00	0.48	0.20				
					37001	1	480.00	481.00	1.00	0.10	0.10				
					37002	1	481.00	482.00	1.00	0.05	0.10				
					37003	1	482.00	483.00	1.00	0.05	0.10				
					37006	1	483.00	484.00	1.00	0.01	0.10				
					37007	1	484.00	485.00	1.00	0.09	0.20				
					37008	1	485.00	486.00	1.00	0.08	0.10				
487.20	493.20	FP	FP	pinkish color, fine grained groundmass, with 1-2mm white feldspar phenocrysts; contact at 20 CA.	37009	1	486.00	487.20	1.20	0.01	0.10				
					37010		487.20	488.00	0.80	0.01	0.10				
					37011		488.00	489.00	1.00	0.01	0.10				
				488.3 1 cm bleb chalcopyrite	37012		489.00	490.00	1.00	0.02	0.10				
					37013		490.00	491.00	1.00	0.01	0.20				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
					37014		491.00	492.00	1.00	0.01	0.20				
					37016		492.00	493.20	1.20	0.01	0.20				
					37017	2	493.20	494.00	0.80	0.01	0.30				
493.20	524.25	Greywacke	GWE	as above:	37018	2	494.00	495.00	1.00	0.07	0.20				
					37019	2	495.00	496.00	1.00	0.06	0.40				
				498-515 weakly altered, pale brownish-red, hematite silicified; 1-3% finely disseminated pyrite; weak crackle breccia.	37020	2	496.00	497.00	1.00	0.08	0.30				
					37021	2	497.00	498.00	1.00	0.09	0.40				
					37022	2	498.00	499.00	1.00	0.19	0.30				
					37023	2	499.00	500.00	1.00	0.01	0.10				
				498.6 2 cm quartz vein at 20 CA	37026	2	500.00	501.00	1.00	0.01	0.20				
					37027	2	501.00	502.00	1.00	0.01	0.20				
					37028	2	502.00	503.00	1.00	0.08	0.10				
				500.8 5 cm quartz vein at 20 CA	37029	2	503.00	504.00	1.00	0.07	0.70				
					37030	2	504.00	505.00	1.00	0.03	0.30				
					37031	2	505.00	506.00	1.00	0.10	0.10				
					37032	2	506.00	507.00	1.00	0.01	0.10				
					37033	2	507.00	508.00	1.00	0.04	0.20				
				505.0 3 cm quartz vein at 20 CA	37034	2	508.00	509.00	1.00	0.01	0.10				
					37036	2	509.00	510.00	1.00	0.04	0.20				
					37037	2	510.00	511.00	1.00	0.08	0.10				
					37038	2	511.00	512.00	1.00	0.33	0.20				
					37039	2	512.00	513.00	1.00	0.23	0.20				
					37040	2	513.00	514.00	1.00	0.30	0.20				
					37041	2	514.00	515.00	1.00	0.71	0.20				
					37042	2	515.00	516.00	1.00	0.26	0.10				
					37043	2	516.00	517.00	1.00	0.27	0.10				
				512.0 1 cm quartz vein at 30 CA	37046	2	517.00	518.00	1.00	0.93	0.20				
				512.1 1 cm quartz vein at 30 CA	37047	2	518.00	519.00	1.00	0.35	0.10				
					37048	2	519.00	520.00	1.00	0.22	0.10				
					37049	2	520.00	521.00	1.00	0.22	0.10				
					37050	2	521.00	522.00	1.00	1.10	0.30				
					37051	2	522.00	523.00	1.00	2.13	0.20				
					37052	2	523.00	524.00	1.00	0.01	0.20				
524.25	556.65	Diabase	DIA	as above:	37053	2	524.00	524.25	0.25	0.01	0.10				
					37054		524.25	525.00	0.75	0.01	0.10				
556.65	558.10	Greywacke:	GWE	as above: contact at 50 CA; Strong Hematite Alteration	37056		556.00	556.65	0.65	0.01	0.10				
				1-3% disseminated pyrite	37057	2	556.65	557.65	1.00	0.01	0.10				
558.10	558.85	Diabase	DIA	as above:	37058	2	557.65	558.10	0.45	0.06	0.10				
					37059		558.10	558.85	0.75	0.04	0.10				
558.85	559.40	Greywacke	GWE	as above	37060	2	558.85	559.40	0.55	0.02	0.10				
					37061	1	573.90	575.00	1.10	0.01	0.30				
559.40	573.90	Diabase	DIA	as above: contact at 50 CA	37062	1	575.00	576.00	1.00	0.01	0.10				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
573.90	578.42	Greywacke	CKZ	strong hematite alteration; 1-2% pyrite;	37063	1	576.00	577.00	1.00	0.01	0.10				
					37064	1	577.00	578.00	1.00	0.01	0.30				
					37067	1	578.00	578.42	0.42	0.01	0.30				
578.42	578.60	FZ	FZ	strongly sheared at 60 CA; clay gouge	37068	1	578.42	578.60	0.18	0.01	0.40				
					37069	1	578.60	579.00	0.40	0.01	0.10				
578.60	587.10	Greywacke	GWE	medium grey, fine grained, possible mixed diabase and greywacke	37070	1	579.00	580.00	1.00	0.01	0.20				
					37071	1	580.00	581.00	1.00	0.01	0.10				
587.10	600.00	Greywacke	CKZ	similar to 573.9-578.42; strong hematite-silicified alteration with 1-3% pyrite	37072	1	581.00	582.00	1.00	0.01	0.10				
					37073	1	582.00	583.00	1.00	0.02	0.20				
					37074	1	583.00	584.00	1.00	0.01	0.50				
					37075	1	584.00	585.00	1.00	0.01	0.30				
					37077	1	585.00	586.00	1.00	0.03	0.20				
					37078	1	586.00	587.00	1.00	0.04	0.10				
					37079	2	587.00	588.00	1.00	0.12	0.70				
					37080	2	588.00	589.00	1.00	0.03	0.50				
					37081	2	589.00	590.00	1.00	0.01	0.40				
					37082	2	590.00	591.00	1.00	0.01	0.40				
					37083	2	591.00	592.00	1.00	0.01	0.30				
					37084	2	592.00	593.00	1.00	0.02	0.30				
					37087	2	593.00	594.00	1.00	0.01	0.30				
				EOH	37088	2	594.00	595.00	1.00	0.01	0.20				
					37089	2	595.00	596.00	1.00	0.01	0.20				
				core stored at Matachewan	37090	2	596.00	597.00	1.00	0.01	0.10				
					37091	2	597.00	598.00	1.00	0.01	0.20				
					37092	2	598.00	599.00	1.00	0.01	0.20				
					37093	2	599.00	600.00	1.00	0.01	0.10				
Downhole Tests:															
	Depth	AZ	DIP												
	51	152.8	-62.8												
	102	152	-62.7												
	150	156.2	-63.1												
	201	155.2	-63.2												
	250	159.1	-63.2												
	300	161.5	-63.4												
	354	159.9	-63.5												
	402	161.1	-63.5												
	450	164.2	-63.5												
	501	165.6	-63.4												
	552	168	-63.5												
	600	171.3	-63.4												

Opawica Explorations Inc.

Matachewan

DDH#: OPW-07-020

Az and Dip: 330/-50

E.O.H: 300 m

GRID LOCATION: Powell Twp., Ontario

GRID: OPW: 0 15+50S

UTM, type: 0522569E, 5311483N: Nad: 83 Zone: 17

Elev.:

Claim: MR37456

Drill Company: Downing: NQ Core

Logged by: Fred Sharpley

Start: August 14, 2007; End: August 18, 2007

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
0.00	3.70		OVB												
					37094		5.10	5.68	0.58	0.03	0.5				
3.70	5.10	CGL	CGL	medium grey, pebbles siltstone, greywacke, syenite < 3 cm in a greywacke matrix	37095		5.68	6.50	0.82	0.11	0.4				
					37096		6.50	7.50	1.00	0.20	1.0				
5.10	5.68	FP	FP	pinkish color, coarse grained pink feldspar phenocrysts < 1 cm; in a reddish groundmass; contact at 60 CA	37097		7.50	8.00	0.50	0.01	0.1				
					37098		8.00	8.70	0.70	0.16	1.5				
				5% quartz veining at 50 CA	37099		8.70	9.70	1.00	0.04	0.6				
					37100		9.70	10.70	1.00	0.05	0.8				
5.68	6.50	Cgl	CGL	as above:	37101		10.70	11.70	1.00	0.12	2.3				
					37102		11.70	12.60	0.90	0.01	0.3				
6.50	8.70	Mafic Dike	MAF	dark green, massive, uniform, contact at 50 CA; 5% quartz veining 50 CA	37104		12.60	13.00	0.40	0.01	0.2				
					37105		13.00	14.00	1.00	0.01	0.1				
					37106		14.00	15.00	1.00	0.01	0.1				
8.70	12.60	Cgl	Cgl	as above	37107		15.00	16.00	1.00	0.01	0.1				
					37108		16.00	17.00	1.00	0.01	0.1				
12.60	23.30	FP	FP	as above	37109		17.00	18.00	1.00	0.07	0.3				
					37110		18.00	19.00	1.00	0.04	0.3				
					37111		19.00	20.00	1.00	0.01	0.2				
					37114		20.00	21.00	1.00	0.02	0.2				
					37115		21.00	22.00	1.00	0.01	0.1				
					37116		22.00	23.00	1.00	0.01	0.2				
					37117		23.00	23.30	0.30	0.01	0.3				
23.30	34.35	Mafic Dike	MAF	as above	37118		34.35	35.00	0.65	0.11	1.9	0.264			
					37119		35.00	36.00	1.00	0.10	1.9	0.270			
34.35	39.20	Siltstone	SILT	as above: Alteration Zone: strongly silicified: 5% quartz veining at 20 CA; massive blebs of chalcopyrite < 3 cm; in quartz veins	37120		36.00	37.00	1.00	0.45	5.3	0.534			
					37121		37.00	38.00	1.00	0.15	4.4	0.469			
					37122		38.00	39.20	1.20	0.23	1.6	0.141			
					37124		40.95	42.00	1.05	0.12	0.6	0.061			
39.20	40.95	Diabase	DIA	as above: contact at 60 CA	37125		42.00	43.30	1.30	0.04	0.7	0.027			
					37126	8	110.40	111.00	0.60	0.10	1.1				
					37127	8	111.00	112.00	1.00	0.04	0.5				
40.95	43.30	Siltstone	SILT	similar to 34.35-39.20: Alteration Zone	37128	8	112.00	113.00	1.00	0.04	0.4				
					37129	8	113.00	114.00	1.00	0.01	0.2				
43.30	67.90	Diabase	DIA	as above:	37130	8	114.00	115.00	1.00	0.01	0.3				
					37131	8	115.00	116.00	1.00	0.01	0.2				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
67.90	68.70	FP	FP	as above:	37134	8	116.00	117.00	1.00	0.02	0.2				
					37135	8	117.00	118.00	1.00	0.01	0.3				
68.70	108.60	Diabase	DIA	as above	37136	8	118.00	119.00	1.00	0.02	0.4				
					37137	8	119.00	120.00	1.00	0.01	0.7				
				68.70-100.00 numerous quartz carbonate veinlets at 50, 80 and parallel CA.	37138	8	120.00	121.00	1.00	0.04	0.7				
					37139	8	121.00	122.00	1.00	0.06	1.6				
					37140	8	122.00	123.00	1.00	0.09	1.9				
108.60	110.40	Fault Zone:	FZ	dark greenish grey, strongly sheared at 40 CA; strongly brecciated	37141	8	123.00	124.00	1.00	0.02	0.9				
					37142	8	124.00	125.00	1.00	0.05	0.7				
					37144	8	125.00	126.00	1.00	0.08	0.3				
110.40	143.34	Siltstone	SILT	Strong Brecciated Alteration Zone: strongly sericitized minor green carbonate; 5-15% finely disseminated pyrite.	37145	8	126.00	127.00	1.00	0.01	0.4				
					37146	8	127.00	128.00	1.00	0.01	0.7				
					37147	8	128.00	129.00	1.00	0.01	0.7				
					37148	8	129.00	130.00	1.00	0.03	1.5				
					37149	8	130.00	131.00	1.00	0.02	0.6				
					37150	8	131.00	132.00	1.00	0.01	0.7				
					37151	8	132.00	133.00	1.00	0.02	0.8				
					37154	8	133.00	134.00	1.00	0.02	0.4				
					37155	8	134.00	135.00	1.00	0.01	0.4				
					37156	8	135.00	136.00	1.00	0.01	0.2				
					37157	8	136.00	137.00	1.00	0.01	0.2				
					37158	8	137.00	138.00	1.00	0.01	0.2				
					37159	8	138.00	139.00	1.00	0.01	0.1				
					37160	8	139.00	140.00	1.00	0.01	0.1				
					37161	8	140.00	141.00	1.00	0.01	0.2				
					37162	8	141.00	142.00	1.00	0.01	0.2				
143.34	143.45	Fault Zone	FZ	strongly sheared at 30 CA; brecciated	37164	8	142.00	143.00	1.00	0.01	0.2				
					37165		143.00	143.45	0.45	0.02	0.3				
143.45	168.85	Diabase	DIA	as above: numerous quartz carbonate veins	37166	2	168.85	169.60	0.75	0.08	0.7				
					37167	2	169.60	170.60	1.00	0.01	0.2				
168.85	170.60	Siltstone	SILT	as above: bleach altered; 1-3% disseminated pyrite; contact at 40 CA	37168	1	290.60	291.00	0.40	0.01	0.3				
					37169	1	291.00	292.00	1.00	0.01	0.1				
					37170	1	292.00	293.00	1.00	0.01	0.2				
170.60	290.60	Diabase	DIA	as above:	37171	1	293.00	294.00	1.00	0.01	0.2				
					37174	1	294.00	295.00	1.00	0.01	0.2				
				190.92-191.06 felsic Dike: light pinkish grey, fine grained massive, uniform; contact at 50 CA	37175	1	295.00	296.00	1.00	0.01	0.1				
					37176	1	296.00	297.00	1.00	0.01	0.2				
					37177	1	297.00	298.00	1.00	0.01	0.3				
290.60	300.00	Siltstone	SILT	medium grey, fine grained, weakly banded at 40 CA; 1-2% disseminated pyrite	37178	1	298.00	299.00	1.00	0.01	0.3				
					37179	1	299.00	300.00	1.00	0.01	0.3				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
				EOH											
				core stored at Matachewan											
Downhole Tests:															
	Depth	AZ	DIP												
	51	328.3	-49.5												
	102	328	-47.8												
	153	331.8	-45.5												
	201	333.3	-43.5												
	252	338.6	-42												
	300	342	-40.3												

Opawica Explorations Inc.

Matachewan

GRID LOCATION: Powell Twp., Ontario

Claim: L373507

DDH#: OPW-07-021

UTM, type: 0522170E, 5311303N: Nad: 83 Zone: 17

Drill Company: Downing: NQ Core

Az and Dip: 330/-70

GRID: OPW: 394W 15+15S

Logged by: Fred Sharpley

E.O.H: 702 m

Elev.:

Start: August 23, 2007; End: September 05, 2007

From	To	Rock Type	Code	Description	Sample#	Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
0.00	3.00		OVB												
					44661		68.00	69.00	1.00	0.03	0.10				
3.00	47.60	CGL	CGL	medium grey, fine grained matrix of greywacke with pebbles of siltstone, syenite <5 cm	44662		69.00	70.00	1.00	0.01	0.20				
					44663		70.00	71.00	1.00	0.01	0.30				
47.60	52.90	GWE	GWE	medium grey, fine grained, fairly massive uniform	44664		71.00	72.00	1.00	0.03	0.20				
					44665		72.00	73.00	1.00	0.01	0.10				
52.90	54.60	Mafic Dike	MAF	dark green, fairly massive uniform; contact at 60 CA	44666		73.00	74.00	1.00	0.01	0.10				
					44667		74.00	75.00	1.00	0.01	0.10				
54.60	59.26	Greywacke	GWE	as above; a few pebbles	44668		75.00	76.00	1.00	0.01	0.20				
					44669		76.00	77.30	1.30	0.01	0.20				
59.26	62.40	Mafic Dike	MAF	as above: 70% Dike, 30% Greywacke: moderately sheared at 60 CA	44671		86.00	87.30	1.30	0.09	0.10				
					44672		87.30	87.53	0.23	0.01	0.30				
62.40	65.80	Greywacke	GWE	as above: pinkish color	44673		87.53	88.10	0.57	0.01	0.20				
					44674		88.10	89.10	1.00	0.01	0.10				
65.80	66.60	Fault Zone	FZ	strongly sheared quartz carbonate veining at 30 CA	44675		89.10	90.00	0.90	0.01	0.10				
					44676		188.00	189.00	1.00	0.01	0.80				
66.60	77.30	Greywacke	GWE	as above:	44677		189.00	190.00	1.00	0.05	0.50				
					44678		190.00	191.00	1.00	0.12	0.80				
				68.50-77.30 20% quartz veining at 30 CA	44681		191.00	192.00	1.00	0.20	0.50				
					44682		192.00	193.00	1.00	0.11	1.10				
					44683		193.00	194.00	1.00	0.08	0.70				
77.30	89.10	CGL	CGL	as above:	44684		194.00	195.00	1.00	0.07	0.50				
					44685		195.00	196.00	1.00	0.02	0.70				
				86.0-87.3 5% quartz veining at 20 CA	44686		196.00	197.00	1.00	0.01	0.80				
				87.3-87.56 Mafic Dike: as above: sheared contact at 30 CA	44687		197.00	198.00	1.00	0.01	0.20				
					44688		198.00	199.00	1.00	0.02	0.20				
				87.56-89.1 10% quartz veining at 20-40 CA	44689		199.00	200.00	1.00	0.01	0.20				
89.10	99.00	Mafic Dike	MAF	as above: Sheared contact at 30 CA; 5% quartz veins	44691		200.00	201.00	1.00	0.01	0.70				
					44692		201.00	202.00	1.00	0.01	0.20				
99.00	108.00	CGL	CGL	as above:	44693		202.00	203.00	1.00	0.02	0.30				
					44694		203.00	203.50	0.50	0.01	0.30				
108.00	139.70	Greywacke	GWE	as above: scattered pebbles: Pebble Greywacke	44695	1	523.35	524.50	1.15	0.01	0.20				
					44696	1	524.50	525.00	0.50	0.03	0.30				

From	To	Rock Type	Code	Description	Sample#	Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
139.70	186.00	Diabase	DIA	dark grey, medium grained, massive uniform;	44697	1	525.00	526.00	1.00	0.33	0.20				
				contact at 30 CA	44698	1	526.00	527.00	1.00	0.10	0.50				
186.00	188.00	Fault Zone	FZ	strongly sheared at 30 CA; brecciated	44701		527.00	528.00	1.00	0.20	1.10				
188.00	203.50	Greywacke	GWE	as above: hematized, silicified	44702		528.00	529.00	1.00	0.09	0.50				
					44703		529.00	530.00	1.00	0.06	0.80				
				188.4 3 cm quartz vein at 30 CA	44704		530.00	531.00	1.00	0.05	0.30				
				189.7 1 cm quartz vein at 30 CA	44705		531.00	532.00	1.00	0.01	0.50				
				197.6 2 cm quartz vein at 30 CA	44706		532.00	533.20	1.20	0.01	0.20				
					44707		541.90	542.50	0.60	0.01	0.20				
					44708	2	554.00	555.00	1.00	0.04	0.60				
203.50	520.70	Diabase	DIA	as above:	44710	2	555.00	556.00	1.00	0.08	0.40				
					44711	2	556.00	557.00	1.00	0.05	0.90				
520.70	533.20	CGL	CGL	as above: 1% disseminated pyrite	44712	2	557.00	558.00	1.00	0.01	0.70				
					44713	2	558.00	559.00	1.00	0.04	0.20				
				523.35-524.18 Diabase	44714	2	574.00	575.00	1.00	0.27	1.80	0.260			
					44715		575.00	576.30	1.30	0.06	0.50	0.046			
533.20	541.90	Diabase	DIA	as above: fine grained	44716		576.30	577.00	0.70	0.02	0.30	0.003			
					44717		577.00	578.00	1.00	0.02	0.10	0.002			
				535.40-536.40 Conglomerate:	44720		578.00	579.00	1.00	0.01	0.20	0.001			
					44721		579.00	580.00	1.00	0.02	0.10	0.002			
				537.060-538.60 Conglomerate:	44722		580.00	581.00	1.00	0.02	0.10	0.002			
					44723		581.00	582.00	1.00	0.01	0.10	0.003			
541.90	576.30	Siltstone	SILT	light grey, fine grained, massive, weakly banded at	44724		582.00	583.00	1.00	0.02	0.10	0.004			
				30-40 CA	44725		583.00	584.00	1.00	0.02	0.10	0.001			
					44726		584.00	585.00	1.00	0.01	0.10	0.008			
				541.90-541.20 white quartz vein at 30 CA	44727		585.00	585.60	0.60	0.02	0.10	0.002			
					44728		585.60	586.00	0.40	0.01	0.20	0.007			
				554.00-559.00 1-3% disseminated pyrite	44730		586.00	586.70	0.70	0.01	0.20	0.010			
					44731		586.70	587.00	0.30	0.01	0.10	0.004			
				574.6-575.1 disseminated pyrite, chalcopyrite with	44732		587.00	588.00	1.00	0.01	0.10	0.003			
				quartz carbonate veins and chlorite at 80 and 50 CA	44733		588.00	589.00	1.00	0.01	0.10	0.005			
					44734		589.00	590.00	1.00	0.01	0.10	0.005			
576.30	585.60	FP	FP	pink feldspar phenocrysts < 1cm in a medium grey	44735		590.00	591.00	1.00	0.01	0.10	0.004			
				groundmass; contact at 30 CA	44736		591.00	592.00	1.00	0.01	0.10	0.010			
					44737		592.00	592.80	0.80	0.03	0.10	0.001			
				577.95 1 cm quartz vein at 60 CA	44740		592.80	594.00	1.20	0.01	0.10				
					44741		594.00	595.00	1.00	0.01	0.20				
				578.3 1 cm quartz vein at 60 CA	44742		595.00	596.00	1.00	0.01	0.30				
					44743		596.00	597.00	1.00	0.02	0.20				
				580.2-580.3 quartz vein at 60 CA	44744	3	597.00	598.00	1.00	0.05	0.20				
					44745	3	598.00	599.00	1.00	0.02	0.10				
				583.94 - 584 quartz vein at 60 CA	44746	3	599.00	600.00	1.00	0.01	0.20				

From	To	Rock Type	Code	Description	Sample#	Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
				584.13 2 cm quartz vein at 60 CA	44747	2	600.00	601.00	1.00	0.01	0.20				
					44748	2	601.00	602.00	1.00	0.01	0.10				
				584.3 5 cm quartz vein at 60 CA	44750	3	602.00	602.86	0.86	0.01	0.20				
				584.9-585.1 quartz vein at 60 CA	44751		602.86	603.70	0.84	0.11	1.40				
585.60	586.70	Mafic Dike	MAF	black color, very fine grained, massive uniform; sharp contact at 20 CA	44752		603.70	604.70	1.00	0.21	1.90				
					44753		604.70	605.50	0.80	0.07	1.10				
586.70	602.86	FP	FP	as above	44754		605.50	606.00	0.50	0.07	1.20				
				587.3 4 cm quartz vein at 60 CA	44755		606.00	607.12	1.12	0.04	0.80				
				588.16-588.26 quartz vein at 60 CA	44756	2	607.12	607.97	0.85	0.23	1.90				
				588.8-589.2 Mafic Dike: as above	44757	2	607.97	609.00	1.03	0.01	0.90				
				590.9-591.1 Mafic Dike: as above	44760	1	609.00	610.00	1.00	0.05	0.80				
				591.75 1 cm quartz vein at 60 CA; trace chalcopyrite	44761		635.00	635.50	0.50	0.04	0.90				
				592.2-592.8 silicified	44762		635.50	636.00	0.50	0.01	1.10				
				pink color, fine grained massive uniform; contact at	44763		636.00	637.00	1.00	0.01	0.20				
				30 CA; from 593-602.86	44764		637.00	638.00	1.00	0.01	0.80				
					44765		638.00	639.00	1.00	0.01	0.70				
				596.1-596.2 quartz vein at 60 Ca											
				597.6 3 cm quartz vein at 60 CA											
				598.0 2 cm quartz vein at 60 CA											
				598.1 2 cm quartz vein at 60 CA											
				598.4 4 cm quartz vein at 60 CA											
				600.0 2 cm quartz vein at 60 CA											
				600.1 2 cm quartz vein at 60 CA											
602.86	604.70	Mafic Dike	MAF	as above: contact at 60 CA											
604.70	607.12	Siltstone	SILT	as above: 1-3% disseminated pyrite; contact at 70-80 CA											
607.12	607.97	Mafic Dike	MAF	as above:											
607.97	635.50	Siltstone	SILT	as above: weakly banded at 20-30 CA											
635.50	638.00	FP	FP	as above: contact at 80 and 30 CA											
				635.5 3 cm quartz vein at 40 CA											
				635.9-636.6 Quartz vein at 40 CA											
638.00	697.50	Siltstone	SILT	as above:											
				664.0-665.0 weak bleach alteration with breccia											
697.50	702.00	FP	FP	pinkish color, fine grained grey to pink matrix with											

From	To	Rock Type	Code	Description	Sample#	Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
				coarse grained pink and white feldspar phenocrysts											
				sharp contact at 50 CA											
				EOH											
				core stored at Matachewan											
Downhole tests:															
	Depth	AZ	DIP												
	51	330	-69.8												
	105	330.9	-69.6												
	150	329.5	-69.5												
	204	332.2	-69.3												
	255	331.7	-69												
	300	332.2	-69.1												
	354	332.2	-69.1												
	402	332.2	-69.1												
	450	332.4	-68.6												
	504	333.5	-68.4												
	550	332.9	-68.2												
	603	333.5	-67.9												
	651	332.7	-67.6												
	702	333.1	-67.5												

Opawica Explorations Inc.

Matachewan
DDH#: OPW-07-022
Az and Dip: 330/-60
E.O.H: 651 m

GRID LOCATION: Powell Twp., Ontario
GRID: OPW: 586W 17+37S
UTM, type: 0522221E, 5311014N: Nad: 83 Zone: 17
Elev.: 322

Claim: MR5400
Drill Company: Downing: NQ Core
Start: September 06, 2007; End: September 14, 2007
Logged by: Fred Sharpley

From	To	Rock Type	Code	Description	Sample#	% Sul		From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %	
0.00	1.50		OVB														
					44766			2.00	3.00	1.00	0.03	0.4					
1.50	3.00	CGL	CGL	dark greenish-grey, fine grained matrix with pebbles of siltstone <3 cm;	44767			5.00	6.00	1.00	0.02	0.6					
					44768			8.00	9.00	1.00	0.01	0.5					
					44769			9.00	10.00	1.00	0.03	0.8					
3.00	8.00	Fault Zone	FZ	strongly sheared at 20-30 CA; 66% core recovery	44770			10.00	11.00	1.00	0.05	0.1					
					44771			12.90	13.60	0.70	0.21	0.7					
8.00	11.00	CGL	CGL	as above: weak to moderately sheared at 30 CA	44772			13.60	14.00	0.40	0.03	0.4					
					44773			14.00	15.00	1.00	0.05	0.6					
11.00	17.00	Fault Zone:	FZ	as above: 60% core recovery	44774			15.00	16.00	1.00	0.01	0.4					
					44776			24.00	25.00	1.00	0.43	0.9					
				12.90-13.60 50% quartz veining at 30 CA	44777			25.00	26.00	1.00	0.55	1.1					
					44778			37.00	37.50	0.50	0.04	0.1					
					44779			37.50	38.00	0.50	0.02	0.2					
17.00	69.00	CGL	CGL	as above:	44780			38.00	39.00	1.00	0.02	0.5					
					44781			39.00	40.00	1.00	0.03	0.4					
				17.0-30.0 weakly sheared at 30 CA	44782			40.00	41.00	1.00	0.08	1.1					
					44783			73.40	74.00	0.60	0.03	0.5					
				37.1-37.5 70% quartz veining at 50 CA	44786	1		74.00	75.00	1.00	0.01	0.9					
				37.7 1 cm quartz vein at 30 CA	44787	1		75.00	76.00	1.00	0.01	0.3					
					44788	1		76.00	77.00	1.00	0.01	0.3					
				39.5 1 cm quartz vein at 30 CA	44789	1		77.00	78.00	1.00	0.04	0.7					
				40.06 1 cm quartz vein at 30 CA	44790	1		78.00	79.00	1.00	0.01	0.6					
				68.4-69.3 core broken up	44791	1		79.00	80.00	1.00	0.01	0.7					
69.00	73.40	Diabase	DIA	dark greenish-grey, fine grained, massive uniform; sharp contact at 20 CA	44792	1		80.00	80.40	0.40	0.01	0.7					
					44793	7		165.00	165.70	0.70	0.01	0.5					
					44794	7		165.70	166.00	0.30	0.01	0.5					
73.40	80.40	CGL	CGL	as above: 1% disseminated pyrite	44796	7		166.00	167.00	1.00	0.01	0.2					
					44797	7		167.00	168.00	1.00	0.01	0.2					
					44798	7		168.00	169.00	1.00	0.01	0.7					
80.40	165.70	Diabase	DIA	as above:	44799	7		169.00	170.00	1.00	0.01	0.1					
					44800	3		170.00	171.00	1.00	0.01	0.1					
165.70	185.30	Syenite	SYN	fine grained, mauve color, massive uniform; sharp contact at 30 CA; 3-5% finely disseminated pyrite;	44801	3		171.00	172.00	1.00	0.01	0.1					
				moderately silicified	44802	3		172.00	173.00	1.00	0.01	0.2					
					44803	3		173.00	174.00	1.00	0.01	0.1					
					44806	3		174.00	175.00	1.00	0.01	0.1					
				165.70-169.7 pinkish color; 5-10 % disseminated pyrite	44807	3		175.00	176.00	1.00	0.01	0.1					

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
				numerous 5mm quartz veinlets at 50 CA; at 166.97, 167.4, 167.45, 167.7, 168.4, 168.5, 168.7, 168.85, 169	44808	3	176.00	177.00	1.00	0.01	0.1				
					44809	3	177.00	178.00	1.00	0.01	0.1				
					44810	3	178.00	179.00	1.00	0.01	0.1				
				169.70-180.0 mauve color, 3-5% fine pyrite; numerous 5mm quartz veins at 50 CA; 3-5%	44811	3	179.00	180.00	1.00	0.01	0.1				
					44812	5	180.00	181.00	1.00	0.01	0.1				
					44813	5	181.00	182.00	1.00	0.01	0.1				
				180.00-185.3 strong red color, 4-7% finely disseminated pyrite; numerous quartz veinlets < 5mm at 50 CA; 5%	44814	5	182.00	183.00	1.00	0.01	0.1				
					44816	5	183.00	184.00	1.00	0.01	0.1				
					44817	5	184.00	185.00	1.00	0.01	0.1				
				182.30 5cm quartz carbonate vein at 20 CA	44818	5	185.00	185.30	0.30	0.01	0.1				
					44819		185.30	186.00	0.70	0.01	0.1				
					44820		197.00	198.00	1.00	0.01	0.1				
				185.10 7 cm quartz carbonate vein at 50 CA	44821	2	198.00	199.00	1.00	0.01	0.1				
					44822		199.00	200.00	1.00	0.01	0.1				
185.30	197.00	Diabase	DIA	as above: contact at 10 CA	44823		200.00	201.00	1.00	0.01	0.1				
					44826		201.00	202.20	1.20	0.02	0.1				
197.00	198.00	Syenite	SYN	as above: pinkish color, fine grained, massive uniform contact at 10 CA	44827	2	202.20	203.00	1.00	0.03	0.1				
				197.50-197.70 diabase	44828	2	203.00	204.00	1.00	0.11	0.1				
				as above: fine grained	44829	2	204.00	205.00	1.00	0.01	0.1				
198.00	202.20	Diabase	DIA	as above: fine grained	44830	2	205.00	206.00	1.00	0.01	0.1				
					44831	2	206.00	207.00	1.00	0.01	0.1				
202.20	208.80	Syenite	SYN	pale pink, fine grained, strongly foliated at 40 CA; brecciated; 1-3% disseminated pyrite	44832	2	207.00	208.00	1.00	0.01	0.1				
					44833	2	208.00	208.80	1.00	0.01	0.1				
					44834		208.80	210.00	1.20	0.13	0.1				
				206.15-206.40 quartz carbonate vein at 40 CA	44836	1	229.30	230.25	0.95	0.3	0.7				
				206.90-207.80 Diabase	44837	2	271.00	272.00	1.00	0.07	0.1				
					44838	3	272.00	273.00	1.00	0.03	0.1				
208.80	229.30	Diabase	DIA	as above:	44839		273.00	274.00	1.00	0.07	0.2				
					44840	2	343.30	344.00	0.70	0.01	0.1				
					44841	2	344.00	345.00	1.00	0.01	0.1				
229.30	230.25	Syenite	SYN	as above: contact at 80 CA; 1% disseminated pyrite	44842	2	345.00	346.00	1.00	0.01	0.1				
					44843	2	346.00	347.00	1.00	0.01	0.1				
230.25	254.00	Diabase	DIA	as above:	44846	2	347.00	348.00	1.00	0.01	0.1				
					44847	2	348.00	349.00	1.00	0.01	0.1				
				230.25-240.00 numerous slips at 30 CA; sheared	44848	2	349.00	350.00	1.00	0.02	0.1				
					44849	2	350.00	351.00	1.00	0.01	0.1				
				248.00-251.00 numerous slips at 30 CA; sheared	44850	2	351.00	352.00	1.00	0.01	0.1				
					44851	2	352.00	353.00	1.00	0.01	0.3				
254.00	257.70	CGL	CGL	as above: chloritized; contact at 30 CA	44852	2	353.00	354.00	1.00	0.01	0.2				
					44853	2	354.00	355.00	1.00	0.01	0.2				
257.70	259.60	Diabase	DIA	as above: strongly foliated at 30 CA; contact at 30 CA	44854	2	355.00	356.00	1.00	0.01	0.6				
					44856	1	356.00	357.00	1.00	0.01	0.2				
259.60	261.80	CGL	CGL	as above: contact at 30 CA	44857	1	357.00	358.00	1.00	0.01	0.4				
					44858	1	358.00	359.00	1.00	0.01	0.2				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
261.80	269.30	Diabase	DIA	as above: strongly foliated; contact at 30 CA	44859	1	359.00	360.00	1.00	0.02	0.1				
					44860	1	360.00	361.00	1.00	0.01	0.1				
269.30	278.30	CGL	CGL	as above: contact at 30 CA	44861	1	361.00	362.00	1.00	0.01	0.1				
					44862	1	362.00	363.00	1.00	0.01	0.1				
				272.8-273.1 3-5% disseminated pyrite	44863	1	363.00	364.00	1.00	0.01	0.4				
					44866	1	364.00	365.00	1.00	0.01	0.1				
278.30	280.40	FP	FP	coarse grained pink feldspar phenocrysts in medium grey groundmass; contact at 40 CA	44867	1	365.00	366.00	1.00	0.01	0.1				
					44868	1	366.00	367.00	1.00	0.01	0.1				
					44869	1	367.00	368.00	1.00	0.01	0.1				
280.40	290.40	CGL	CGL	as above:	44870	1	368.00	369.00	1.00	0.01	0.1				
					44871	1	369.00	370.00	1.00	0.01	0.2				
290.40	323.60	Fault Zone	FZ	core totally broken up; oxidized, brecciated; sheared at 50 CA; 50% recovery	44872	1	370.00	371.00	1.00	0.01	0.2				
					44873	1	371.00	371.90	0.90	0.01	0.1				
				309.0-323.60 75% recovery; Conglomerate:	44874	1	500.00	501.00	1.00	0.01	0.2				
					44876	5	501.00	502.00	1.00	0.04	1.4				
323.60	343.30	Diabase	DIA	as above: contact at 50 CA	44877	1	502.00	503.00	1.00	0.02	0.5				
					44878	1	503.00	504.00	1.00	0.01	0.4				
				323.60-324.6 strongly foliated at 50 CA;	44879	1	504.00	505.00	1.00	0.01	0.1				
					44880	1	505.00	506.00	1.00	0.01	0.1				
343.30	371.90	CGL	CGL	as above: pebbles of siltstone, syenite <5 cm	44881	1	506.00	507.00	1.00	0.01	0.5				
					44882	1	507.00	508.00	1.00	0.01	0.4				
				343.30-352.00 weakly altered, bleached with pale grey and pale green; 1-3% disseminated pyrite	44883	1	508.00	509.00	1.00	0.01	0.3				
					44886	1	509.00	510.00	1.00	0.01	0.7				
				352.0-365.0 1-3% finely disseminated pyrite	44887	1	510.00	511.00	1.00	0.01	0.4				
					44888	1	511.00	512.00	1.00	0.01	0.4				
					44889	1	512.00	513.00	1.00	0.01	0.3				
371.90	493.65	Diabase	DIA	medium to dark grey, fine to medium grained, massive uniform; contact at 30 CA	44890	10	513.00	514.00	1.00	0.01	0.2				
					44891	15	514.00	515.00	1.00	0.04	1.2				
					44892	30	515.00	516.00	1.00	0.05	3.7				
					44893	30	516.00	517.00	1.00	0.07	4.4				
					44894	30	517.00	518.00	1.00	0.1	15.4				
					44896	20	518.00	519.00	1.00	0.01	1.1				
					44897	20	519.00	520.00	1.00	0.06	4.8				
				477.0-490.5 fine grained, 5% red hematite streaks	44898	20	520.00	521.00	1.00	0.01	2				
				478.5 trace of chalcopyrite	44899	8	521.00	522.00	1.00	0.01	1.1				
					44900	8	522.00	523.00	1.00	0.02	2.1				
493.65	512.00	CGL	CGL	medium grey matrix with pebbles of siltstone, red syenite < 5 cm	44901	8	523.00	524.00	1.00	0.01	1				
					44902	8	524.00	525.00	1.00	0.01	0.4				
					44903	8	525.00	526.00	1.00	0.02	0.3				
				502.75 1 cm quartz vein at 40 CA	44906	5	526.00	527.00	1.00	0.01	0.3				
				508.40 1 cm quartz vein at 40 CA	44907	5	527.00	528.00	1.00	0.02	1				
				509.1 1 cm quartz vein at 50 CA	44908	5	528.00	529.00	1.00	0.02	0.9				
				510.55 1 cm quartz vein at 50 CA	44909	5	529.00	530.00	1.00	0.01	0.8				
					44910	5	530.00	531.00	1.00	0.01	0.1				

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
512.00	522.00	CGL	CGL	as above: pebbles siltstone, chert, syenite <5 cm;	44911	5	531.00	532.00	1.00	0.01	0.2	0.010			
				green carbonate fragments <1cm; hematite streaks;	44912	5	532.00	533.00	1.00	0.01	0.2	0.008			
				Strong Sericite-Silicified Alteration; 10-30 %	44913	5	533.00	534.00	1.00	0.01	0.3	0.011			
				disseminations and stringers of pyrite	44914	5	534.00	535.00	1.00	0.01	0.1	0.007			
					44916	2	535.00	536.00	1.00	0.01	0.2	0.014			
					44917	2	536.00	537.00	1.00	0.01	0.7	0.006			
522.00	534.00	CGL	CGL	as above: pebbles siltstone, chert, syenite <5 cm;	44918	2	537.00	538.00	1.00	0.01	0.5	0.007			
				Moderate Sericite-Silicified Alteration; 5-10 %	44919	2	538.00	539.00	1.00	0.01	0.4	0.011			
				disseminated pyrite	44920	2	539.00	540.00	1.00	0.01	0.2	0.012			
					44921	2	540.00	541.00	1.00	0.01	0.2	0.012			
				527.40-527.60 sheared at 20 CA	44922	2	541.00	542.00	1.00	0.01	0.1	0.009			
					44923	2	542.00	543.00	1.00	0.01	0.3	0.009			
					44924	2	543.00	544.00	1.00	0.01	0.3	0.008			
					44927	2	544.00	545.00	1.00	0.01	0.3	0.021			
					44928	2	545.00	546.00	1.00	0.01	0.2	0.010			
					44929	2	546.00	547.00	1.00	0.01	0.5	0.009			
					44930	2	547.00	548.00	1.00	0.01	0.1	0.005			
					44931	2	548.00	549.00	1.00	0.01	0.1	0.012			
					44932	2	549.00	550.00	1.00	0.01	0.5	0.015			
					44933	2	550.00	551.00	1.00	0.01	0.3	0.017			
					44934	2	551.00	552.00	1.00	0.01	0.2	0.004			
534.00	606.00	CGL	CGL	light grey, Weak Sericite-Silicified Alteration, pebbles	44935	2	552.00	553.00	1.00	0.01	0.3	0.008			
				siltstone, chert; weakly brecciated; 1-3% disseminated	44937	2	553.00	554.00	1.00	0.01	0.2	0.003			
				pyrite	44938	2	554.00	555.00	1.00	0.01	0.1	0.003			
					44939	2	555.00	556.00	1.00	0.03	0.3	0.010			
					44940	2	556.00	557.00	1.00	0.01	0.1	0.014			
					44941	2	557.00	558.00	1.00	0.02	0.5	0.024			
					44942	2	558.00	559.00	1.00	0.01	0.3	0.025			
					44943	2	559.00	560.00	1.00	0.01	0.2	0.016			
					44944	2	560.00	561.00	1.00	0.01	0.3	0.015			
					44947	2	561.00	562.00	1.00	0.03	0.7	0.018			
					44948	2	562.00	563.00	1.00	0.02	0.2	0.022			
					44949	2	563.00	564.00	1.00	0.03	0.4	0.016			
					44950	2	564.00	565.00	1.00	0.01	0.5	0.015			
					44951	2	565.00	566.00	1.00	0.01	0.7	0.018			
					44952	2	566.00	567.00	1.00	0.01	0.3	0.020			
					44953	2	567.00	568.00	1.00	0.02	0.5	0.019			
					44954	2	568.00	569.00	1.00	0.01	0.6	0.021			
					44955	5	569.00	570.00	1.00	0.01	0.4	0.016			
					44957	5	570.00	571.00	1.00	0.01	0.5	0.020			
					44958	5	571.00	572.00	1.00	0.01	0.5	0.031			
					44959	5	572.00	573.00	1.00	0.01	0.6	0.017			
				570.0-598.50 brecciated, 5-15% disseminations and	44960	5	573.00	574.00	1.00	0.01	0.4	0.044			
				stringers pyrite; weak to moderate quartz-sericite	44961	5	574.00	575.00	1.00	0.03	0.7	0.047			

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
				alteration	44962	5	575.00	576.00	1.00	0.01	0.2	0.017			
					44963	5	576.00	577.00	1.00	0.01	0.2	0.022			
				592.8-592.9 sheared breccia at 40 CA	44964	5	577.00	578.00	1.00	0.03	0.5	0.027			
					44967	5	578.00	579.00	1.00	0.01	0.2	0.019			
					44968	5	579.00	580.00	1.00	0.01	0.3	0.014			
					44969	5	580.00	581.00	1.00	0.02	0.2	0.006			
					44970	5	581.00	582.00	1.00	0.01	0.1	0.021			
					44971	5	582.00	583.00	1.00	0.01	0.3	0.007			
					44972	5	583.00	584.00	1.00	0.01	0.5	0.009			
					44973	5	584.00	585.00	1.00	0.02	0.8	0.012			
					44974	5	585.00	586.00	1.00	0.03	1.1	0.027			
					44975	5	586.00	587.00	1.00	0.01	0.7	0.015			
					44977	5	587.00	588.00	1.00	0.01	0.9	0.019			
					44978	5	588.00	589.00	1.00	0.02	0.8	0.013			
					44979	5	589.00	590.00	1.00	0.03	0.8	0.013			
					44980	5	590.00	591.00	1.00	0.01	0.9	0.009			
					44981	15	591.00	592.00	1.00	0.01	1.2	0.007			
					44982	15	592.00	593.00	1.00	0.01	1.6	0.008			
					44983	15	593.00	594.00	1.00	0.06	2.3	0.019			
					44984	15	594.00	595.00	1.00	0.01	1.8	0.010			
					44987	15	595.00	596.00	1.00	0.03	1	0.008			
					44988	15	596.00	597.00	1.00	0.03	1.5	0.012			
					44989	15	597.00	598.00	1.00	0.03	1.1	0.016			
				600.30-610.00 brecciated, 5-15% disseminations and stringers pyrite; weak to moderate quartz-sericite alteration	44990	15	598.00	599.00	1.00	0.04	1.1	0.019			
					44991	5	599.00	600.00	1.00	0.01	0.5	0.015			
					44992	5	600.00	601.00	1.00	0.01	0.5	0.012			
					44993	15	601.00	602.00	1.00	0.03	1	0.014			
					44994	15	602.00	603.00	1.00	0.01	0.7	0.013			
					44995	15	603.00	604.00	1.00	0.05	1	0.001			
					44997	5	604.00	605.00	1.00	0.04	0.7	0.018			
606.00	618.10	CGL	CGL	as above: pebbles siltstone, chert, syenite <5 cm; numerous red syenite pebbles, strongly silicified	44998	5	605.00	606.00	1.00	0.04	0.7	0.023			
					44999	15	606.00	607.00	1.00	0.01	0.5	0.011			
					45000	15	607.00	608.00	1.00	0.05	0.8	0.047			
					45001	15	608.00	609.00	1.00	0.04	0.5	0.011			
					45002	15	609.00	610.00	1.00	0.06	0.6	0.021			
					45003	15	610.00	611.00	1.00	0.04	0.3	0.009			
					45004	15	611.00	612.00	1.00	0.05	0.5	0.017			
					45007	15	612.00	613.00	1.00	0.01	0.1	0.015			
				613.60 traces chalcopyrite	45008	15	613.00	614.00	1.00	0.01	0.1	0.014			
					45009	10	614.00	615.00	1.00	0.01	0.3	0.011			
618.10	651.00	Diabase	DIA	as above: medium grained; contact at 30 CA	45010	10	615.00	616.00	1.00	0.01	1.1	0.010			
					45011	10	616.00	617.00	1.00	0.01	0.8	0.014			
					45012	10	617.00	618.10	1.10	0.01	0.5	0.016			
					45013		618.10	619.00	0.90	0.01	0.4	0.023			

From	To	Rock Type	Code	Description	Sample#	% Sul	From	To	m	Au g/t	AG g/t	Cu %	Zn %	Pb %	Mo %
				EOH											
				core stored at Matachewan;											
				hole deepened from 600.0-651.0 from September 22 to											
				September 27, 2007; casing left in hole											
Downhole Tests:															
	Depth	AZ	DIP												
	54.00	330.2	-59.9												
	102.00	330	-60												
	153.00	330.9	-59.9												
	204.00	330.5	-61												
	252.00	332.6	-60												
	300.00	332.1	-59.7												
	351.00	333	-59.5												
	402.00	332.7	-59.2												
	453.00	332.5	-59.2												
	504.00	335.5	-59.1												
	552.00	337.4	-58.9												
	600.00	339.2	-58.4												
	651.00	340.6	-58.1												

Appendix B

Assay Certificates

7W-2278-RA1	2 pages	7W-2832-RA1	2 pages
7W-2279-RA1	2 pages	7W-2833-RA1	2 pages
7W-2280-RA1	2 pages	7W-2834-RA1	2 pages
7W-2281-RA1	1 page	7W-2835-RA1	2 pages
7W-2290-RA1	3 pages	7W-2866-RA1	2 pages
7W-2291-RA1	2 pages	7W-2867-RA1	2 pages
7W-2419-RA1	2 pages	7W-2884-RA1	2 pages
7W-2420-RA1	3 pages	7W-2885-RA1	2 pages
7W-2421-RA1	3 pages	7W-2886-RA1	2 pages
7W-2516-RA1	3 pages	7W-2887-RA1	2 pages
7W-2517-RA1	3 pages	7W-2888-RA1	1 page
7W-2518-RA1	2 pages	7W-2889-RA1	2 pages
7W-2520-RA1	3 pages	7W-2890-RA1	2 pages
7W-2521-RA1	3 pages	7W-3105-RA1	3 pages
7W-2522-RA1	1 page	7W-3106-RA1	2 pages
7W-2544-RA1	3 pages	7W-3107-RA1	2 pages
7W-2545-RA1	3 pages	7W-3108-RA1	1 page
7W-2546-RA1	3 pages	7W-3109-RA1	2 pages
7W-2547-RA1	3 pages	7W-3110-RA1	1 page
7W-2548-RA1	3 pages	7W-3111-RA1	2 pages
7W-2696-RA1	3 pages	7W-3112-RA1	2 pages
7W-2697-RA1	3 pages	7W-3113-RA1	3 pages
7W-2698-RA1	2 pages	7W-3115-RA1	1 page
7W-2699-RA1	2 pages	7W-3116-RA1	1 page
7W-2700-RA1	2 pages	7W-3117-RA1	1 page
7W-2701-RA1	2 pages	7W-3118-RA1	2 pages
7W-2702-RA1	2 pages	7W-3119-RA1	2 pages
7W-2703-RA1	1 page	7W-3120-RA1	2 pages
7W-2769-RA1	3 pages	7W-3121-RA1	2 pages
7W-2770-RA1	3 pages	7W-3122-RA1	2 pages
7W-2771-RA1	3 pages	7W-3123-RA1	2 pages
7W-2772-RA1	3 pages	7W-3124-RA1	2 pages
7W-2829-RA1	2 pages	7W-3125-RA1	2 pages
7W-2830-RA1	3 pages	7W-3214-RA1	2 pages
7W-2831-RA1	2 pages	7W-3215-RA1	1 page



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

7W-2278-RA1

Assay Certificate

Company: **OPAWICA RESOURCES LTD**

Project:

Attn: F. Sharpley

Date: JUL-09-07

Welsh

We hereby certify the following Assay of 55 Core samples submitted JUN-29-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
34001	Nil	-	0.1
34002	Nil	0.01	0.4
34003	Nil	-	0.1
34004	Nil	-	0.2
34005	0.03	-	0.4
34006	Nil	-	0.3
34007	0.06	0.04	1.3
34008	Nil	-	0.5
34009	0.02	-	1.0
34010	0.64	-	1.5
34011	Nil	-	0.8
34012	Nil	-	0.5
34013	Nil	-	0.3
34014	Nil	-	0.1
34015	0.02	-	0.1
34016	0.01	-	0.3
34017	0.01	Nil	0.3
34018	Nil	-	0.1
34019	Nil	-	0.1
34020	Nil	-	0.1
34021	0.01	-	0.2
34022	Nil	-	0.3
34023	Nil	-	0.2
34024	0.01	-	0.1
34025	Nil	-	0.5
34026	Nil	-	0.4
34027	Nil	Nil	0.1
34028	Nil	-	0.4
34029	Nil	-	0.1
34030	2.82	-	0.1

Certified by *Dennis Christy*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

7W-2278-RA1

Company: **OPAWICA RESOURCES LTD**

Date: JUL-09-07

Project:

Attn: F. Sharpley

Welsh

We hereby certify the following Assay of 55 Core samples submitted JUN-29-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
34031	Nil	-	0.1
34032	0.01	-	0.1
34033	Nil	-	0.1
34034	Nil	-	0.1
34035	Nil	-	0.1
34036	0.14	0.13	0.1
34037	Nil	-	0.1
34038	0.04	-	0.1
34039	0.03	-	0.1
34040	0.04	-	0.1
34041	Nil	-	0.1
34042	0.03	-	0.1
34043	Nil	-	0.1
34044	0.02	-	0.3
34045	Nil	-	0.7
34046	Nil	-	0.7
34047	Nil	-	0.4
34048	Nil	0.01	1.1
34049	Nil	-	2.1
34050	0.01	-	2.5
34051	0.62	-	0.7
34052	Nil	-	1.5
34053	Nil	-	1.3
34054	Nil	-	0.8
34055	Nil	-	1.3
Blank	Nil	-	-
STD 0xJ47	2.47	-	-

Certified by *Dennis Chate*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

7W-2279-RA1

Assay Certificate

Company: **OPAWICA RESOURCES LTD**

Project:

Attn: F. Sharpley

Date: JUL-09-07

Welsh

We hereby certify the following Assay of 55 Core samples submitted JUN-29-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
34056	0.02	-	1.3
34057	0.01	-	1.7
34058	0.02	0.01	2.1
34059	Nil	-	0.8
34060	Nil	-	1.2
34061	Nil	-	1.3
34062	Nil	-	0.1
34063	0.02	-	1.3
34064	0.01	-	0.7
34065	Nil	-	1.1
34066	Nil	-	1.3
34067	0.02	-	1.9
34068	0.03	-	1.4
34069	0.03	-	1.2
34070	Nil	-	1.1
34071	Nil	-	1.2
34072	1.84	-	33.6
34073	Nil	-	0.9
34074	Nil	-	0.9
34075	0.01	-	1.8
34076	0.03	-	1.1
34077	0.03	-	1.9
34078	0.05	-	1.5
34079	0.02	-	1.4
34080	Nil	-	1.2
34081	Nil	-	1.2
34082	Nil	-	0.1
34083	Nil	-	1.1
34084	Nil	Nil	0.4
34085	0.01	-	0.2

Certified by *Dennis Chant*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

7W-2279-RA1

Company: **OPAWICA RESOURCES LTD**

Date: JUL-09-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 55 Core samples submitted JUN-29-07 by .

Welsh

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
34086	Nil	-	0.1
34087	0.02	-	0.1
34088	Nil	Nil	0.2
34089	Nil	-	0.1
34090	Nil	-	0.4
34091	Nil	-	1.2
34092	4.07	-	0.9
34093	Nil	-	0.5
34094	Nil	-	0.2
34095	Nil	-	0.1
34096	0.03	-	0.2
34097	Nil	-	0.3
34098	Nil	-	0.1
34099	0.03	-	0.2
34100	0.02	-	0.3
34101	0.01	-	0.3
34102	Nil	-	0.1
34103	Nil	-	0.6
34104	0.02	-	0.3
34105	0.05	0.02	0.6
34106	Nil	-	0.4
34107	Nil	-	0.7
34108	Nil	-	0.8
34109	Nil	-	0.8
34110	Nil	-	0.8
Blank	Nil	-	-
STD OxJ47	2.33	-	-

Certified by *Dennis Christie*

File - OXW - Project -
Maitikwan - Assays 1)



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

7W-2280-RA1

Company: **OPAWICA RESOURCES LTD**
Project:
Attn: F. Sharpley

Date: JUL-10-07

We hereby certify the following Assay of 55 Core samples submitted JUN-29-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
34111	0.06	0.06	1.1
34112	0.68	-	1.4
34113	0.01	-	1.5
34114	0.01	-	0.6
34115	0.01	-	0.1
34116	0.01	-	0.1
34117	0.01	-	0.4
34118	0.01	-	0.1
34119	0.01	-	0.1
34120	0.01	-	0.1
34121	0.01	-	0.1
34122	0.01	-	0.1
34123	0.01	0.01	0.1
34124	0.01	-	0.1
34125	0.02	-	3.2
34126	0.01	-	0.1
34127	0.01	-	0.1
34128	0.01	-	0.1
34129	0.01	-	0.1
34130	0.01	-	0.1
34131	0.01	-	0.1
34132	2.84	-	0.1
34133	0.01	0.01	0.1
34134	0.01	-	0.1
34135	0.01	-	0.1
34136	0.01	-	0.1
34137	0.01	-	0.1
34138	0.01	-	0.1
34139	0.43	0.36	0.1
34140	0.04	-	0.7

Certified by 



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

7W-2280-RA1

Company: **OPAWICA RESOURCES LTD**

Project:

Attn: F. Sharpley

Date: JUL-10-07

Welsh

We hereby certify the following Assay of 55 Core samples submitted JUN-29-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
34141	0.06	-	0.8
34142	0.01	-	0.1
34143	0.07	-	0.1
34144	0.01	-	0.1
34145	0.01	-	0.1
34146	0.03	-	0.1
34147	0.20	0.26	0.1
34148	0.01	-	0.1
34149	0.01	-	0.1
34150	0.01	-	0.1
34151	0.01	0.01	0.1
34152	0.60	-	0.7
34153	0.01	-	0.5
34154	0.06	-	0.1
34155	0.01	-	0.1
34156	0.01	-	0.1
34157	0.01	-	0.1
34158	0.01	-	0.1
34159	0.01	-	0.7
34160	0.01	-	0.8
34161	0.01	-	1.0
34162	0.01	-	0.1
34163	0.02	-	3.4
34164	0.01	0.01	0.1
34165	0.01	-	0.1
Blank	0.01	-	-
STD OxJ47	2.40	-	-

Certified by

[Signature]



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Assay Certificate

7W-2281-RA1

Company: **OPAWICA RESOURCES LTD**

Date: JUL-10-07

Project:
Attn: F. Sharpley

Welsh

We hereby certify the following Assay of 25 Core samples submitted JUN-29-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
34166	0.04	-	0.1
34167	0.03	-	4.1
34168	0.01	-	0.1
34169	0.01	-	0.1
34170	0.04	-	0.1
34171	0.01	-	0.1
34172	1.80	-	32.9
34173	0.01	-	0.1
34174	0.06	0.05	0.3
34175	0.02	-	0.4
34176	0.01	-	0.1
34177	0.01	-	0.4
34178	0.06	-	0.2
34179	0.08	-	0.1
34180	0.09	-	0.3
34181	0.13	0.14	0.2
34182	0.01	-	0.1
34183	0.03	-	0.2
34184	0.04	-	0.2
34185	0.04	-	0.4
34186	0.09	-	1.2
34187	0.10	-	1.3
34188	0.05	0.04	0.4
34189	0.01	-	0.4
34190	0.08	-	0.7
Blank	0.01	-	-
STD OxJ47	2.31	-	-

Certified by *[Signature]*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

7W-2290-RA1

Assay Certificate

Company: **OPAWICA RESOURCES LTD**

Date: JUL-10-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 73 Core samples submitted JUL-04-07 by .

Welsh

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
34371	0.01	-	0.2
34372	1.80	-	33.4
34373	0.01	-	0.1
34374	0.01	-	0.1
34375	0.02	-	0.5
34376	0.01	-	0.3
34377	0.01	-	0.1
34378	0.03	-	0.1
34379	0.02	0.01	0.1
34380	0.08	-	0.2
34381	0.05	-	0.3
34382	0.01	-	0.1
34383	0.01	-	0.1
34384	0.01	-	0.4
34385	0.01	-	0.8
34386	0.03	-	0.7
34387	0.01	-	0.1
34388	0.04	-	0.1
34389	0.01	-	0.1
34390	0.01	0.01	0.1
34391	0.01	-	0.1
34392	4.11	-	1.3
34393	0.03	-	0.1
34394	0.02	-	0.1
34395	0.01	-	0.1
34396	0.14	-	0.1
34397	0.09	0.07	0.1
34398	0.01	-	0.1
34399	0.01	-	0.1
34400	0.01	-	0.1

Certified by

[Signature]



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

Assay Certificate

7W-2290-RA1

Company: **OPAWICA RESOURCES LTD**

Date: JUL-10-07

Project:

Attn: F. Sharpley

Welsh

We hereby certify the following Assay of 73 Core samples submitted JUL-04-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
34471	0.01	-	0.5
34472	0.01	-	0.3
34473	1.79	-	33.3
34474	0.04	0.03	0.3
34475	0.01	-	0.4
34476	0.01	-	0.1
34477	0.01	-	0.1
34478	0.01	-	0.1
34479	0.01	-	0.1
34480	0.01	-	0.4
34481	0.01	-	0.2
34482	0.01	-	0.1
34483	0.01	-	0.1
34484	0.01	-	0.6
34485	0.01	0.01	0.4
34486	0.01	-	0.1
34487	0.01	-	0.3
34488	0.01	-	0.1
34489	0.01	-	0.2
34490	0.01	0.01	0.2
34491	0.01	-	0.1
34492	0.01	-	0.1
34493	4.18	-	1.0
34494	0.01	-	0.1
34495	0.01	-	0.1
34496	0.01	-	0.4
34497	0.01	-	0.1
34498	0.01	-	0.1
34499	0.01	0.01	0.1
34500	0.01	-	0.1

Certified by _____

[Handwritten Signature]



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

7W-2290-RA1

Assay Certificate

Company: **OPAWICA RESOURCES LTD**

Date: JUL-10-07

Project:

Attn: F. Sharpley

Welsh

We hereby certify the following Assay of 73 Core samples submitted JUL-04-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
34501	0.01	-	0.1
34502	0.01	-	0.1
34503	0.01	-	0.1
34504	0.01	-	0.4
34505	0.01	0.01	0.1
34506	0.01	-	0.2
34507	0.01	-	0.1
34508	0.01	-	0.1
34509	0.01	-	0.3
34510	0.01	-	0.1
34511	0.01	-	0.2
34512	0.61	-	1.5
34513	0.01	0.01	0.2
Blank	0.01	-	-
STD OXJ47	2.32	-	-

Certified by _____



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

7W-2291-RA1

Assay Certificate

Company: **OPAWICA RESOURCES LTD**

Project:

Attn: F. Sharpley

Date: JUL-12-07

Welsh

We hereby certify the following Assay of 47 Core samples submitted JUL-04-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
34514	Nil	-	0.3
34515	Nil	-	0.3
34516	Nil	-	0.1
34517	Nil	-	0.1
34518	Nil	-	0.1
34519	0.03	0.01	0.1
34520	0.02	-	0.1
34521	0.02	-	0.1
34522	Nil	-	0.1
34523	Nil	-	0.1
34524	Nil	-	0.1
34525	Nil	-	0.1
34526	0.01	-	0.1
34527	0.03	-	0.1
34528	0.03	-	0.1
34529	Nil	-	0.1
34530	Nil	-	0.1
34531	Nil	-	0.1
34532	2.78	-	0.1
34533	Nil	-	0.2
34534	0.12	-	0.1
34535	0.10	-	0.1
34536	0.01	-	0.1
34537	0.05	-	0.1
34538	0.11	-	0.1
34539	0.02	-	0.1
34540	0.02	0.03	0.1
34541	0.02	-	0.1
34542	Nil	-	0.1
34543	Nil	-	0.1

Certified by *Dennis Chanty*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

7W-2291-RA1

Company: **OPAWICA RESOURCES LTD**

Project:

Attn: F. Sharpley

Date: JUL-12-07

Welsh

We hereby certify the following Assay of 47 Core samples submitted JUL-04-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
34544	Nil	-	0.1
34545	0.03	-	0.1
34546	Nil	Nil	0.1
34547	Nil	-	0.1
34548	Nil	-	0.1
34549	0.01	-	0.1
34550	Nil	-	0.1
34551	Nil	-	0.1
34552	0.60	-	0.8
34553	Nil	Nil	0.1
34554	Nil	-	0.1
34555	Nil	-	0.1
34556	Nil	-	0.1
34557	Nil	-	0.1
34558	0.05	-	0.1
34559	Nil	-	0.1
34560	Nil	-	0.1
Blank	Nil	-	-
STD OxJ47	2.39	-	-

Certified by *Dennis Christy*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

7W-2419-RA1

Assay Certificate

Company: **OPAWICA EXPLORATIONS INC.**
Project:
Attn: F. Sharpley

Date: JUL-26-07

Welsh

We hereby certify the following Assay of 34 Core samples submitted JUL-11-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
34651	0.02	-	0.1
34652	0.01	0.01	0.1
34653	0.02	-	0.1
34654	0.01	-	0.1
34655	0.01	-	0.1
34656	0.01	-	0.1
34657	0.01	-	0.1
34658	0.01	-	0.1
34659	0.01	-	0.1
34660	0.01	-	0.1
34661	0.01	-	0.1
34662	0.01	-	0.1
34663	0.01	-	0.1
34664	0.02	-	0.1
34665	0.03	-	0.1
34666	0.01	-	0.1
34667	0.06	0.04	0.1
34668	0.12	-	0.2
34669	0.05	-	0.1
34670	1.73	-	33.2
34671	0.01	-	0.1
34672	0.01	-	0.1
34673	0.01	-	0.1
34674	0.01	-	0.1
34675	0.01	-	0.1
34676	0.02	0.03	0.1
34677	0.02	-	0.1
34678	0.01	-	0.1
34679	0.01	-	0.1
34680	0.01	-	0.1

Certified by *Devin Charles*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

7W-2419-RA1

Date: JUL-26-07

Assay Certificate

Company: **OPAWICA EXPLORATIONS INC.**
Project:
Attn: F. Sharpley

Welsh

We hereby certify the following Assay of 34 Core samples submitted JUL-11-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
34681	0.02	-	0.2
34682	0.01	-	0.1
34683	0.01	-	0.1
34684	0.01	0.01	0.1
Blank	0.01	-	-
STD OxJ47	2.29	-	-

Certified by *Dennis Chant*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

Assay Certificate

7W-2420-RA1

Company: **OPAWICA RESOURCES INC.**

Date: JUL-26-07

Project:

Attn: F. Sharpley

Welsh

We hereby certify the following Assay of 74 Core samples submitted JUL-11-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM	Cu PPM
34685	0.04	0.05	0.8	226
34686	0.08	-	0.4	202
34687	0.19	-	0.3	90
34688	0.47	-	1.0	298
34689	0.81	-	1.6	364
34690	Nil	-	0.4	327
34691	0.08	-	0.2	75
34692	0.03	-	0.2	80
34693	0.04	-	0.2	133
34694	4.05	-	0.8	7
34695	0.04	-	0.2	204
34696	0.04	0.03	0.2	137
34697	0.03	-	0.2	104
34698	0.02	-	0.3	156
34699	0.02	-	0.3	102
34700	0.13	-	0.2	159
34701	0.05	-	0.5	190
34702	0.06	-	0.5	237
34703	Nil	-	0.6	233
34704	0.01	-	0.1	11
34705	0.03	-	0.8	517
34706	0.08	-	1.2	433
34707	0.03	-	1.1	171
34708	0.04	-	9.2	527
34709	Nil	-	0.5	159
34710	0.02	-	0.7	122
34711	Nil	-	0.4	183
34712	Nil	0.02	2.1	213
34713	0.02	-	0.2	88
34714	0.62	-	1.5	5180

Certified by *[Signature]*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

7W-2420-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Project:

Attn: F. Sharpley

Date: JUL-26-07

Welsh

We hereby certify the following Assay of 74 Core samples submitted JUL-11-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM	Cu PPM
34715	0.01	-	1.3	129
34716	0.02	-	0.1	6
34717	0.13	-	0.3	3
34718	0.01	-	0.1	3
34719	0.01	-	2.1	245
34720	0.02	-	2.8	151
34721	0.02	-	2.0	76
34722	0.03	-	1.6	171
34723	0.02	-	1.6	182
34724	Nil	-	0.1	10
34725	0.01	Nil	2.1	105
34726	0.04	-	1.7	95
34727	0.11	-	1.0	153
34728	Nil	-	0.6	122
34729	0.02	-	0.8	192
34730	0.01	-	0.8	103
34731	0.02	-	1.0	233
34732	0.03	-	1.2	214
34733	0.03	-	1.8	104
34734	2.79	-	0.1	109
34735	0.02	-	1.0	80
34736	0.08	-	3.2	207
34737	0.02	-	1.0	175
34738	0.02	-	0.7	42
34739	Nil	-	1.0	250
34740	0.01	-	0.5	65
34741	0.02	-	1.1	80
34742	0.05	0.03	1.7	307
34743	0.09	-	1.6	315
34744	Nil	-	0.1	10

Certified by

A. R. New



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

7W-2420-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Date: JUL-26-07

Project:

Attn: F. Sharpley

Welsh

We hereby certify the following Assay of 74 Core samples submitted JUL-11-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM	Cu PPM
34745	0.08	-	1.2	375
34746	0.10	-	1.1	91
34747	0.03	-	1.2	41
34748	0.02	0.02	0.8	36
34749	0.04	-	0.8	79
34750	0.02	-	0.4	53
34751	0.20	-	0.5	355
34752	0.18	-	0.9	183
34753	0.07	-	1.4	134
34754	0.61	-	0.9	11
34755	0.04	-	1.5	61
34756	0.04	0.05	2.0	68
34757	0.09	-	0.8	54
34758	Nil	-	0.5	38
Blank	Nil	-	-	-
STD OxJ47	2.46	-	-	-

Certified by *Denis Chouh*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

Assay Certificate

7W-2421-RA1

Company: **OPAWICA EXPLORATIONS INC.**

Date: JUL-27-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 62 Core samples submitted JUL-11-07 by .

Welsh

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM	Cu PPM
34759	0.03	-	0.3	25
34760	0.21	-	1.1	36
34761	0.04	-	2.4	41
34762	0.02	-	1.6	51
34763	0.03	0.03	1.5	47
34764	0.01	-	0.1	9
34765	0.11	-	1.0	66
34766	0.02	-	1.3	43
34767	0.04	-	1.7	47
34768	0.03	-	1.2	37
34769	0.03	-	2.4	45
34770	0.01	-	1.8	38
34771	0.01	-	1.5	44
34772	0.04	-	2.5	42
34773	0.03	0.04	2.2	46
34774	1.84	-	33.5	6
34775	0.04	-	1.6	52
34776	0.04	-	1.1	52
34777	0.28	-	0.5	231
34778	0.10	-	0.8	78
34779	0.04	-	0.7	45
34780	0.03	-	1.3	77
34781	0.05	-	1.2	115
34782	0.05	-	0.8	105
34783	0.05	-	0.8	104
34784	0.01	-	0.1	10
34785	0.36	0.32	0.4	69
34786	0.11	-	0.5	87
34787	0.02	-	0.7	44
34788	0.02	-	0.9	36

Certified by *Dani Clarke*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

7W-2421-RA1

Assay Certificate

Company: **OPAWICA EXPLORATIONS INC.**

Date: JUL-27-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 62 Core samples submitted JUL-11-07 by .

Welsh

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM	Cu PPM
34789	0.02	-	0.9	40
34790	0.01	-	0.8	32
34791	0.02	-	0.5	45
34792	0.01	-	1.1	37
34793	0.02	-	1.0	61
34794	4.18	-	0.9	6
34795	0.01	-	0.7	91
34796	0.04	-	1.0	31
34797	0.01	-	0.9	77
34798	0.01	-	0.5	177
34799	0.04	-	0.5	88
34800	0.05	-	0.4	71
34801	0.04	-	0.4	70
34802	0.01	-	0.5	177
34803	0.01	-	0.4	159
34804	0.01	-	0.1	10
34805	0.01	-	0.4	22
34806	0.01	-	0.4	23
34807	0.01	-	0.3	21
34808	0.01	0.01	0.4	212
34809	0.01	-	0.5	184
34810	0.01	-	0.8	89
34811	0.01	-	0.7	83
34812	0.01	-	0.9	112
34813	0.01	-	0.9	149
34814	0.62	-	1.5	5210
34815	0.01	0.01	1.0	131
34816	0.04	-	2.4	275
34817	0.01	-	1.6	271
34818	0.01	-	1.1	172

Certified by *Denis Chato*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

7W-2421-RA1

Assay Certificate

Company: **OPAWICA EXPLORATIONS INC.**

Date: JUL-27-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 62 Core samples submitted JUL-11-07 by .

Welsh

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM	Cu PPM
34819	0.01	-	1.3	154
34820	0.01	0.01	0.9	70
Blank	0.01	-	-	-
STD OxJ47	2.44	-	-	-

Certified by *Dennis Christo*

WALKER



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

Assay Certificate

7W-2516-RA1

Date: AUG-16-07

Company: **OPAWICA RESOURCES LTD**
Project:
Attn: F. Sharpley

We hereby certify the following Assay of 72 Core samples submitted JUL-23-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM	Cu PPM
34821	0.01	-	0.8	92
34822	0.01	-	0.1	5
34823	0.01	-	0.1	7
34824	0.01	-	0.1	6
34825	0.01	-	0.1	11
34826	0.04	-	0.1	6
34827	0.01	-	0.1	5
34828	0.01	0.01	0.1	7
34829	0.01	-	0.1	7
34830	0.01	-	0.1	11
34831	0.01	-	0.2	9
34832	0.01	-	2.3	214
34833	0.01	-	1.2	70
34834	2.75	-	0.1	111
34835	0.01	-	1.0	371
34836	0.01	-	1.5	433
34837	0.03	0.04	0.4	759
34838	0.03	-	1.4	2010
34839	0.01	-	0.9	313
34840	0.01	-	0.6	155
34841	0.01	-	0.4	452
34842	0.03	-	0.8	393
34843	0.02	-	1.5	575
34844	0.03	0.03	1.4	581
34845	0.01	-	0.1	7
34846	0.01	-	0.3	343
34847	0.04	-	1.0	152
34848	0.01	-	0.1	146
34849	0.01	-	0.2	120
34850	0.01	-	0.4	363

Certified by *Dennis Chant*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

WALKER

Page 2 of 3

Assay Certificate

7W-2516-RA1

Company: **OPAWICA RESOURCES LTD**

Date: AUG-16-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 72 Core samples submitted JUL-23-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM	Cu PPM
34851	0.04	-	0.3	-
34852	0.05	-	0.1	-
34853	0.04	-	0.4	-
34854	0.01	-	0.1	-
34855	0.62	-	0.8	-
34856	0.02	-	0.1	-
34857	0.01	-	0.1	-
34858	0.01	-	0.1	-
34859	0.01	0.01	0.2	-
34860	0.01	-	0.8	-
34861	0.03	-	0.4	-
34862	0.01	-	0.1	-
34863	0.02	-	0.3	-
34864	0.02	-	0.4	-
34865	0.01	-	0.1	-
34866	0.01	-	0.1	-
34867	0.01	-	0.1	-
34868	0.01	-	0.1	-
34869	0.01	0.01	0.2	-
34870	0.01	-	0.2	-
34871	0.01	-	0.2	-
34872	0.02	-	0.4	-
34873	0.01	-	0.1	-
34874	1.78	-	33.5	-
34875	0.01	-	0.1	-
34876	0.01	-	0.4	-
34877	0.01	-	0.1	-
34878	0.01	-	0.3	-
34879	0.01	-	0.3	-
34880	0.01	0.01	0.5	-

Certified by *Dennis Chast*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

WALKER

Page 3 of 3

Assay Certificate

7W-2516-RA1

Company: **OPAWICA RESOURCES LTD**

Date: AUG-16-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 72 Core samples submitted JUL-23-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM	Cu PPM
34881	0.03	-	0.4	-
34882	0.01	-	0.3	-
34883	0.02	-	0.3	-
34884	0.01	-	0.1	-
34885	0.01	0.01	0.4	-
34886	0.01	-	0.1	-
34887	0.01	-	0.4	-
34888	0.02	-	0.2	-
34889	0.01	-	0.1	-
34890	0.01	0.01	0.2	-
34891	0.01	-	0.2	-
34892	0.01	-	0.3	-
Blank	0.01	-	-	-
STD OxJ47	2.48	-	-	-

Certified by Devin Christy



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

Assay Certificate

7W-2517-RA1

Company: **OPAWICA EXPLORATIONS INC.**

Date: JUL-26-07

Project:

Attn: F. Sharpley

Welsh

We hereby certify the following Assay of 73 Core samples submitted JUL-23-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
34893	0.02	-	0.1
34894	4.15	-	0.9
34895	0.01	-	0.1
34896	0.01	-	0.1
34897	0.01	-	0.1
34898	0.01	-	0.1
34899	0.02	-	0.1
34900	0.02	-	0.1
34901	0.04	-	0.1
34902	0.03	0.01	0.3
34903	0.03	-	0.4
34904	0.01	-	0.1
34905	0.01	-	0.3
34906	0.03	-	0.2
34907	0.02	-	0.3
34908	0.03	-	0.2
34909	0.01	-	0.2
34910	0.04	-	0.4
34911	0.02	-	0.3
34912	0.01	-	0.4
34913	0.01	-	0.3
34914	0.63	-	1.6
34915	0.02	-	0.3
34916	0.01	0.01	0.2
34917	0.01	-	0.1
34918	0.01	-	0.7
34919	0.01	-	0.7
34920	0.03	-	0.4
34921	0.02	0.03	0.7
34922	0.04	-	0.4

Welsh

Welsh

Walker

Certified by *[Signature]*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

Assay Certificate

7W-2517-RA1

Company: **OPAWICA EXPLORATIONS INC.**

Date: JUL-26-07

Project:

Attn: F. Sharpley

Walker

We hereby certify the following Assay of 73 Core samples submitted JUL-23-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
34923	0.01	-	0.2
34924	0.01	-	0.1
34925	0.01	-	0.3
34926	2.92	-	0.1
34927	0.01	-	0.1
34928	0.02	-	0.6
34929	0.01	0.01	0.9
34930	0.01	-	0.1
34931	0.01	-	0.1
34932	0.01	-	0.1
34933	0.01	-	0.1
34934	0.01	-	0.1
34935	0.01	-	0.1
34936	0.01	-	0.1
34937	0.01	-	0.1
34938	0.02	-	0.1
34939	0.01	-	0.2
34940	0.02	-	0.1
34941	0.01	-	0.1
34942	0.02	-	0.1
34943	0.01	0.01	0.1
34944	0.01	-	0.1
34945	0.01	-	0.1
34946	0.62	-	0.8
34947	0.01	-	0.3
34948	0.01	-	0.7
34949	0.02	-	1.5
34950	0.01	-	0.6
34951	0.01	-	0.1
34952	0.01	-	0.1

Certified by

[Signature]



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

Assay Certificate

7W-2517-RA1

Company: **OPAWICA EXPLORATIONS INC.**
Project:
Attn: F. Sharpley

Date: JUL-26-07

Walker

We hereby certify the following Assay of 73 Core samples submitted JUL-23-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
34953	0.01	-	0.1
34954	0.01	-	0.1
34955	0.01	-	0.1
34956	0.01	-	0.1
34957	0.01	-	0.1
34958	0.01	-	0.1
34959	0.01	-	0.1
34960	0.01	-	0.1
34961	0.01	-	0.2
34962	0.01	-	1.0
34963	0.01	-	0.5
34964	0.01	0.01	0.1
34965	0.01	-	0.1
Blank	0.01	-	-
STD OxJ47	2.31	-	-

Certified by _____

[Signature]



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

7W-2518-RA1

Date: JUL-27-07

Assay Certificate

Company: **OPAWICA EXPLORATIONS INC.**

Project:

Attn: F. Sharpley

Walker

We hereby certify the following Assay of 35 Core samples submitted JUL-23-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
34966	1.79	-	33.8
34967	0.01	-	0.1
34968	0.01	-	0.1
34969	0.01	-	0.1
34970	0.01	-	0.1
34971	0.02	-	0.2
34972	0.01	-	0.1
34973	0.01	0.01	0.1
34974	0.02	-	0.1
34975	0.02	-	0.1
34976	0.01	-	0.1
34977	0.03	-	0.1
34978	0.04	-	0.2
34979	0.03	-	0.1
34980	0.03	-	0.1
34981	0.01	-	0.1
34982	0.04	-	0.1
34983	0.04	-	0.4
34984	0.05	0.05	0.4
34985	0.01	-	0.2
34986	4.18	-	0.9
34987	0.01	-	0.1
34988	0.02	-	0.1
34989	0.01	-	0.2
34990	0.08	0.08	0.1
34991	0.05	-	0.2
34992	0.01	-	0.4
34993	0.01	-	0.2
34994	0.01	-	0.1
34995	0.01	-	0.2

Certified by *Dennis Chisholm*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

7W-2518-RA1

Date: JUL-27-07

Company: **OPAWICA EXPLORATIONS INC.**
Project:
Attn: F. Sharpley

We hereby certify the following Assay of 35 Core samples submitted JUL-23-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
34996	0.01	-	0.1
34997	0.01	-	0.2
34998	0.01	-	0.2
34999	0.01	-	0.1
35000	0.04	0.03	0.2
Blank	0.01	-	-
STD OxJ47	2.35	-	-

Certified by *Dennis Chantre*

1 Cameron Ave., P.O. Box 10, Swastika, Ontario P0K 1T0
Telephone (705) 642-3244 Fax (705) 642-3300



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

Assay Certificate

7W-2520-RA1

Company: **OPAWICA EXPLORATIONS INC.**

Date: JUL-27-07

Project:

Attn: F. Sharpley

Walker

We hereby certify the following Assay of 73 Core samples submitted JUL-23-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
35501	0.04	0.04	0.1
35502	0.03	-	0.1
35503	0.04	-	0.1
35504	0.01	-	0.1
35505	0.03	-	0.1
35506	0.65	-	1.6
35507	0.02	-	0.1
35508	0.03	-	0.1
35509	0.08	-	0.1
35510	0.16	-	0.1
35511	0.06	-	0.1
35512	0.11	0.13	0.1
35513	0.11	-	0.2
35514	0.06	-	0.1
35515	0.07	-	0.1
35516	0.01	-	0.1
35517	0.01	-	0.1
35518	0.04	-	0.1
35519	0.08	-	0.1
35520	0.01	0.02	0.1
35521	0.01	-	0.1
35522	0.04	-	0.1
35523	0.01	-	0.1
35524	0.02	-	0.1
35525	0.01	-	0.1
35526	2.90	-	0.1
35527	0.02	-	0.1
35528	0.01	-	0.1
35529	0.01	-	0.1
35530	0.04	0.03	0.1

Certified by *Dennis Chant*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

7W-2520-RA1

Assay Certificate

Company: **OPAWICA EXPLORATIONS INC.**

Date: JUL-27-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 73 Core samples submitted JUL-23-07 by .

Walker

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
35531	0.02	-	0.1
35532	0.01	-	0.1
35533	0.01	-	0.2
35534	0.01	-	0.1
35535	0.01	-	0.2
35536	0.01	-	0.1
35537	0.01	0.01	0.1
35538	0.02	-	0.3
35539	0.01	-	0.1
35540	0.01	-	0.1
35541	0.02	-	0.1
35542	0.02	-	0.1
35543	0.03	-	0.2
35544	0.03	-	0.1
35545	0.01	-	0.1
35546	0.59	-	1.0
35547	0.01	-	0.1
35548	0.01	-	0.1
35549	0.01	-	0.3
35550	0.01	-	0.2
35551	0.02	0.02	0.3
35552	0.01	-	0.2
35553	0.01	-	0.4
35554	0.01	-	0.4
35555	0.01	-	0.4
35556	0.01	-	0.1
35557	0.01	-	0.1
35558	0.01	-	0.1
35559	0.01	-	0.3
35560	0.01	0.01	0.8

Certified by *Dennis Chantre*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

7W-2520-RA1

Assay Certificate

Company: **OPAWICA EXPLORATIONS INC.**
Project:
Attn: F. Sharpley

Date: JUL-27-07

We hereby certify the following Assay of 73 Core samples submitted JUL-23-07 by .

Walker

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
35561	0.01	-	0.1
35562	0.01	-	0.2
35563	0.01	-	0.1
35564	0.01	-	0.1
35565	0.01	-	0.1
35566	1.81	-	33.8
35567	0.01	-	0.1
35568	0.01	-	0.2
35569	0.01	-	0.2
35570	0.01	-	0.2
35571	0.01	0.01	0.1
35572	0.01	-	0.1
35573	0.01	-	0.1
Blank	0.01	-	-
STD OxJ47	2.31	-	-

Certified by *Dennis Chabot*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

Assay Certificate

7W-2521-RA1

Company: **OPAWICA RESOURCES**

Project:

Attn: F. Sharpley

Date: AUG-02-07

Walker

We hereby certify the following Assay of 74 Core samples submitted JUL-23-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
35574	0.01	-	0.2
35575	0.01	-	0.1
35576	0.01	-	0.1
35577	0.01	-	0.1
35578	0.01	0.01	0.1
35579	0.01	-	0.1
35580	0.01	-	0.2
35581	0.01	-	0.2
35582	0.01	-	0.1
35583	0.01	-	0.1
35584	0.01	-	0.1
35585	0.01	-	0.1
35586	4.18	-	0.9
35587	0.01	-	0.1
35588	0.01	-	0.1
35589	0.01	-	0.1
35590	0.01	-	0.1
35591	0.01	-	0.1
35592	0.01	-	0.1
35593	0.01	0.01	0.1
35594	0.01	-	0.1
35595	0.01	-	0.1
35596	0.01	-	0.1
35597	0.01	-	0.1
35598	0.01	-	0.1
35599	0.01	-	0.1
35600	0.01	-	0.1
35601	0.02	-	0.1
35602	0.01	0.01	0.1
35603	0.01	-	0.1

Certified by *Dennis Chroth*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

7W-2521-RA1

Assay Certificate

Company: **OPAWICA RESOURCES**

Date: AUG-02-07

Project:
Attn: F. Sharpley

Walker

We hereby certify the following Assay of 74 Core samples submitted JUL-23-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
35604	0.01	-	0.1
35605	0.01	-	0.1
35606	0.62	-	1.7
35607	0.01	-	0.1
35608	0.01	-	0.1
35609	0.01	-	0.8
35610	0.01	-	0.4
35611	0.01	0.01	0.4
35612	0.01	-	0.2
35613	0.01	-	0.1
35614	0.01	-	0.3
35615	0.01	-	0.2
35616	0.01	-	0.1
35617	0.01	-	0.2
35618	0.01	0.04	0.1
35619	0.01	-	0.1
35620	0.01	-	0.1
35621	0.01	-	0.2
35622	0.01	-	0.2
35623	0.01	-	0.3
35624	0.01	-	0.4
35625	0.01	-	0.1
35626	2.67	-	0.1
35627	0.01	-	0.1
35628	0.01	-	0.1
35629	0.01	-	0.1
35630	0.01	0.01	0.1
35631	0.01	-	0.1
35632	0.01	-	0.2
35633	0.01	-	0.1

Certified by *Dennis Chant*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

Assay Certificate

7W-2521-RA1

Company: **OPAWICA RESOURCES**

Date: AUG-02-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 74 Core samples submitted JUL-23-07 by :

Walker

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
35634	0.01	-	0.1
35635	0.01	-	0.1
35636	0.01	-	0.1
35637	0.01	-	0.1
35638	0.01	-	0.1
35639	0.01	-	0.1
35640	0.02	-	0.1
35641	0.01	-	0.1
35642	0.01	-	0.1
35643	0.01	-	0.1
35644	0.01	-	0.1
35645	0.01	-	0.2
35646	0.60	-	0.9
35647	0.01	-	0.1
Blank	0.01	-	-
STD OxJ47	2.40	-	-

Certified by

Dennis Christy



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Assay Certificate

WALSH

7W-2522-RA1

Company: **OPAWICA EXPLORATIONS INC.**

Date: JUL-30-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 23 Core samples submitted JUL-23-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
35648	0.01	-	0.2
35649	0.01	-	0.3
35650	0.01	-	0.1
35651	0.01	-	0.7
35652	0.01	-	1.1
35653	0.01	-	1.4
35654	0.01	-	0.1
35655	0.01	-	0.2
35656	0.01	-	0.1
35657	0.01	-	0.4
35658	0.01	-	0.4
35659	0.01	-	0.3
35660	0.01	-	0.4
35661	0.01	-	0.3
35662	0.01	0.01	0.1
35663	0.01	-	0.1
35664	0.01	-	0.1
35665	0.01	-	0.1
35666	1.80	-	33.5
35667	0.01	-	0.1
35668	0.01	0.01	0.1
35669	0.01	-	0.1
35670	0.01	-	0.1
Blank	0.01	-	-
STD OXJ47	2.25	-	-

Certified by Denis Charty



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

7W-2544-RA1

Date: JUL-31-07

Assay Certificate

Company: **OPAWICA EXPLORATIONS INC.**

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 75 Core samples submitted JUL-25-07 by .

Walker

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
35671	0.01	-	0.1
35672	0.01	-	0.1
35673	0.01	-	0.1
35674	0.05	-	0.1
35675	0.05	-	0.1
35676	0.01	-	0.1
35677	0.03	-	0.2
35678	0.02	-	0.1
35679	0.01	0.01	0.1
35680	0.01	-	0.1
35681	0.01	-	0.1
35682	0.02	-	0.1
35683	0.01	-	0.1
35684	0.01	-	0.1
35685	0.01	0.01	0.1
35686	4.13	-	0.9
35687	0.01	-	0.1
35688	0.01	-	0.1
35689	0.01	-	0.1
35690	0.01	-	0.1
35691	0.01	-	0.1
35692	0.01	-	0.1
35693	0.01	0.01	0.1
35694	0.01	-	0.1
35695	0.01	-	0.1
35696	0.01	-	0.1
35697	0.01	-	0.1
35698	0.01	-	0.1
35699	0.01	-	0.1
35700	0.01	-	0.1

Certified by *Dennis Chonka*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

7W-2544-RA1

Assay Certificate

Company: **OPAWICA EXPLORATIONS INC.**

Date: JUL-31-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 75 Core samples submitted JUL-25-07 by .

Walker

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
35701	0.01	-	0.1
35702	0.01	-	0.1
35703	0.02	-	0.1
35704	0.01	-	0.2
35705	0.01	-	0.3
35706	0.59	-	1.6
35707	0.02	-	0.1
35708	0.01	-	0.1
35709	0.02	0.01	0.1
35710	0.01	-	0.1
35711	0.01	-	0.1
35712	0.01	-	0.1
35713	0.01	-	0.1
35714	0.01	-	0.1
35715	0.01	-	0.1
35716	0.01	-	0.1
35717	0.01	-	0.1
35718	0.03	-	0.1
35719	0.03	-	0.2
35720	0.02	-	0.1
35721	0.01	-	0.1
35722	0.01	-	0.1
35723	0.01	0.01	0.1
35724	0.01	-	0.1
35725	0.01	-	0.1
35726	2.77	-	0.1
35727	0.01	-	0.1
35728	0.01	-	0.1
35729	0.01	-	0.2
35730	0.01	-	0.1

Certified by *Dennis Chantre*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

7W-2544-RA1

Assay Certificate

Company: **OPAWICA EXPLORATIONS INC.**

Date: JUL-31-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 75 Core samples submitted JUL-25-07 by .

Walker

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
35731	0.01	0.01	0.1
35732	0.01	-	0.2
35733	0.01	-	0.2
35734	0.01	-	0.2
35735	0.01	-	0.1
35736	0.01	-	0.1
35737	0.01	-	0.1
35738	0.02	-	0.1
35739	0.01	-	0.1
35740	0.01	0.01	0.1
35741	0.01	-	0.1
35742	0.01	-	0.1
35743	0.01	-	0.1
35744	0.01	-	0.1
35745	0.01	-	0.1
Blank	0.01	-	-
STD OxK48	3.58	-	-

Certified by *Dennis Christ*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

Assay Certificate

7W-2545-RA1

Company: **OPAWICA EXPLORATIONS INC.**

Date: JUL-31-07

Project:

Attn: F. Sharpley

Walker

We hereby certify the following Assay of 75 Core samples submitted JUL-25-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
35746	0.62	-	1.0
35747	0.01	-	0.1
35748	0.02	-	0.1
35749	0.02	-	0.2
35750	0.01	0.01	0.1
35751	0.01	-	0.1
35752	0.01	-	0.2
35753	0.01	-	0.4
35754	0.01	-	0.4
35755	0.01	-	0.3
35756	0.01	-	0.1
35757	0.02	-	0.3
35758	0.01	-	0.1
35759	0.01	-	0.1
35760	0.01	-	0.1
35761	0.01	-	0.1
35762	0.01	0.01	0.1
35763	0.01	-	0.1
35764	0.01	-	0.1
35765	0.01	-	0.1
35766	1.78	-	33.8
35767	0.02	-	0.1
35768	0.01	-	0.1
35769	0.01	-	0.1
35770	0.01	-	0.1
35771	0.03	-	0.1
35772	0.01	0.01	0.1
35773	0.01	-	0.1
35774	0.01	-	0.1
35775	0.01	-	0.1

Certified by *Dennis Charters*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

Assay Certificate

7W-2545-RA1

Company: **OPAWICA EXPLORATIONS INC.**

Date: JUL-31-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 75 Core samples submitted JUL-25-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
35776	0.01	-	0.1
35777	0.02	-	0.1
35778	0.01	-	0.1
35779	0.01	-	0.1
35780	0.01	-	0.1
35781	0.01	-	0.1
35782	0.01	-	0.1
35783	0.01	-	0.1
35784	0.01	0.01	0.1
35785	0.01	-	0.1
35786	4.21	-	1.1
35787	0.03	-	0.1
35788	0.01	-	0.1
35789	0.01	-	0.1
35790	0.01	-	0.1
35791	0.01	-	0.1
35792	0.01	-	0.1
35793	0.01	-	0.1
35794	0.01	-	0.1
35795	0.01	0.01	0.1
35796	0.01	-	0.1
35797	0.01	-	0.1
35798	0.01	-	0.2
35799	0.01	-	0.1
35800	0.01	-	0.3
35801	0.01	-	0.1
35802	0.01	-	0.1
35803	0.01	-	0.1
35804	0.01	-	0.1
35805	0.01	0.01	0.2

Certified by Dennis Chantre



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

Assay Certificate

7W-2545-RA1

Company: **OPAWICA EXPLORATIONS INC.**

Date: JUL-31-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 75 Core samples submitted JUL-25-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
35806	0.63	-	1.7
35807	0.01	-	0.2
35808	0.01	-	0.1
35809	0.01	-	0.1
35810	0.01	-	0.1
35811	0.02	-	0.2
35812	0.10	-	0.1
35813	0.16	0.14	0.4
35814	0.05	-	0.1
35815	0.06	-	0.1
35816	0.01	-	0.1
35817	0.01	-	0.1
35818	0.01	-	0.1
35819	0.01	-	0.1
35820	0.01	-	0.1
Blank	0.01	-	-
STD OxK48	3.53	-	-

Certified by Denis Chantre



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

7W-2546-RA1

Date: AUG-10-07

Assay Certificate

Company: **OPAWICA EXPLORATIONS INC.**

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 75 Core samples submitted JUL-25-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
35821	0.03	-	0.1
35822	0.01	-	0.1
35823	0.07	-	0.1
35824	0.05	0.01	0.1
35825	0.03	-	0.1
35826	2.79	-	0.1
35827	0.01	-	0.1
35828	0.02	-	0.1
35829	0.01	-	0.1
35830	0.01	-	0.1
35831	0.01	-	0.1
35832	0.01	-	0.1
35833	0.01	-	0.1
35834	0.01	-	0.1
35835	0.01	-	0.1
35836	0.01	-	0.1
35837	0.01	-	0.1
35838	0.01	-	0.1
35839	0.01	0.01	0.1
35840	0.01	-	0.1
35841	0.02	-	0.1
35842	0.01	-	0.1
35843	0.03	-	0.1
35844	0.01	-	0.1
35845	0.02	0.01	0.1
35846	0.62	-	0.9
35847	0.01	-	0.1
35848	0.01	-	0.1
35849	0.01	-	0.1
35850	0.01	-	0.1

Certified by *Dennis Cloutier*

WELSH



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

7W-2546-RA1

Assay Certificate

Company: **OPAWICA EXPLORATIONS INC.**

Date: AUG-10-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 75 Core samples submitted JUL-25-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
35851	0.02	-	0.1
35852	0.01	-	0.1
35853	0.01	-	0.1
35854	0.02	-	0.1
35855	0.02	-	0.1
35856	0.01	-	0.1
35857	0.02	-	0.1
35858	0.03	-	0.1
35859	0.01	-	0.1
35860	0.06	-	0.4
35861	0.05	-	0.1
35862	0.15	0.17	1.1
35863	0.08	-	0.3
35864	0.21	-	0.1
35865	0.01	-	0.1
35866	1.77	-	33.1
35867	0.01	-	0.1
35868	0.01	-	0.1
35869	0.01	-	0.4
35870	0.01	-	0.1
35871	0.03	-	0.3
35872	0.01	-	0.1
35873	0.03	-	0.1
35874	0.01	-	0.1
35875	0.04	-	0.1
35876	0.01	-	0.1
35877	0.03	-	0.1
35878	0.09	-	0.1
35879	0.01	-	0.1
35880	0.02	-	0.1

Certified by Dennis Chant

Welsh



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

7W-2546-RA1

Assay Certificate

Company: **OPAWICA EXPLORATIONS INC.**

Date: AUG-10-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 75 Core samples submitted JUL-25-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
35881	0.01	-	0.1
35882	0.05	-	0.1
35883	0.01	-	0.3
35884	0.06	-	0.1
35885	3.74	4.18	1.0
35886	0.01	-	0.1
35887	0.01	-	0.2
35888	0.45	0.40	0.1
35889	0.01	-	0.1
35890	0.01	-	0.1
35891	0.01	-	0.1
35892	0.03	-	0.1
35893	0.03	-	0.1
35894	0.03	-	0.1
35895	0.01	-	0.1
Blank	0.01	-	-
STD OxK48	3.54	-	-

Certified by *Dennis Chantre*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

Assay Certificate

7W-2547-RA1

Company: **OPAWICA EXPLORATIONS INC.**

Date: AUG-02-07

Project:

Attn: F. Sharpley

Walker

We hereby certify the following Assay of 75 Core samples submitted JUL-25-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
35896	0.34	-	0.1
35897	0.02	-	0.1
35898	0.02	-	0.1
35899	0.05	-	0.1
35900	0.30	0.33	0.1
35901	0.15	-	0.1
35902	0.20	-	0.2
35903	0.18	-	0.2
35904	0.32	-	0.1
35905	0.59	-	1.8
35906	0.22	-	0.1
35907	0.05	-	0.1
35908	0.02	-	0.1
35909	0.01	-	0.1
35910	0.01	-	0.1
35911	0.01	-	0.2
35912	0.01	0.01	0.1
35913	0.02	-	0.2
35914	0.01	-	0.2
35915	0.01	-	0.1
35916	0.25	-	0.2
35917	0.09	-	0.1
35918	0.04	-	0.1
35919	0.02	-	0.1
35920	0.02	-	0.1
35921	0.03	-	0.1
35922	0.02	-	0.1
35923	0.05	-	0.1
35924	0.01	0.01	0.1
35925	2.67	-	0.1

Certified by *Dani Chait*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

Assay Certificate

7W-2547-RA1

Company: **OPAWICA EXPLORATIONS INC.**

Date: AUG-02-07

Project:

Attn: F. Sharpley

Walker

We hereby certify the following Assay of 75 Core samples submitted JUL-25-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
35926	0.02	-	0.1
35927	0.01	-	0.1
35928	0.04	-	0.1
35929	0.02	-	0.1
35930	0.11	-	0.1
35931	0.01	-	0.3
35932	0.02	0.01	0.1
35933	0.03	-	0.1
35934	0.01	-	0.2
35935	0.01	-	0.1
35936	0.01	-	0.1
35937	0.02	-	0.1
35938	0.02	-	0.1
35939	0.01	-	0.1
35940	0.01	0.02	0.1
35941	0.15	-	0.1
35942	0.03	-	0.1
35943	0.01	-	0.1
35944	0.02	-	0.1
35945	0.58	-	0.8
35946	0.04	-	0.1
35947	0.01	-	0.1
35948	0.01	-	0.1
35949	0.01	-	0.1
35950	0.01	-	0.1
35951	0.01	0.01	0.1
35952	0.01	-	0.1
35953	0.08	-	0.1
35954	0.07	-	0.2
35955	0.01	-	0.1

Certified by *Dennis Chantre*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

Assay Certificate

7W-2547-RA1

Company: **OPAWICA EXPLORATIONS INC.**
Project:
Attn: F. Sharpley

Date: AUG-02-07

We hereby certify the following Assay of 75 Core samples submitted JUL-25-07 by .

Walker

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
35956	0.01	-	0.1
35957	0.01	-	0.1
35958	0.01	-	0.1
35959	0.01	-	0.1
35960	0.04	-	0.1
35961	0.02	-	0.1
35962	0.01	-	0.1
35963	0.01	-	0.4
35964	0.01	-	0.3
35965	1.75	-	33.4
35966	0.05	-	0.1
35967	0.10	-	0.2
35968	0.10	-	0.1
35969	0.02	-	0.1
35970	0.01	-	0.2
Blank	0.01	-	-
STD OxK48	3.51	-	-

Certified by *Dennis Chatter*

WELSM



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

Assay Certificate

7W-2548-RA1

Company: **OPAWICA EXPLORATIONS INC.**


Date: AUG-08-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 80 Core samples submitted JUL-25-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
35971	0.01	-	0.1
35972	0.04	-	0.1
35973	0.01	-	0.1
35974	0.02	-	0.1
35975	0.01	-	0.1
35976	0.01	-	0.1
35977	0.01	0.01	0.2
35978	0.01	-	0.7
35979	0.01	-	0.1
35980	0.01	-	0.1
35981	0.01	-	0.3
35982	0.01	-	0.1
35983	0.01	-	0.1
35984	0.01	-	0.1
35985	3.97	-	1.1
35986	0.01	-	0.4
35987	0.01	0.01	0.1
35988	0.01	-	0.1
35989	0.02	-	0.1
35990	0.01	-	0.1
35991	0.02	-	0.1
35992	0.01	-	0.1
35993	0.01	-	0.1
35994	0.01	-	0.1
35995	0.01	-	0.1
35996	0.01	0.01	0.1
35997	0.01	-	0.1
35998	0.06	-	0.1
35999	0.06	-	0.1
36000	0.03	-	0.1

Certified by 



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

Assay Certificate

7W-2548-RA1

Company: **OPAWICA EXPLORATIONS INC.**
 Project:
 Attn: F. Sharpley

Date: AUG-08-07

We hereby certify the following Assay of 80 Core samples
 submitted JUL-25-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
36001	0.01	-	0.1
36002	0.01	-	0.1
36003	0.01	-	0.1
36004	0.01	-	0.1
36005	0.64	-	1.7
36006	0.01	-	0.1
36007	0.01	-	0.1
36008	0.01	-	0.1
36009	0.01	-	0.1
36010	0.01	-	0.1
36011	0.03	-	0.1
36012	0.03	0.01	0.1
36013	0.01	-	0.1
36014	0.02	-	0.1
36015	0.01	-	0.1
36016	0.01	-	0.1
36017	0.01	-	0.1
36018	0.03	-	0.1
36019	0.01	-	0.1
36020	0.06	-	0.1
36021	0.01	-	0.1
36022	0.01	-	0.1
36023	0.01	-	0.1
36024	0.01	-	0.1
36025	2.89	-	0.1
36026	0.01	-	0.1
36027	0.01	-	0.1
36028	0.01	-	0.1
36029	0.01	-	0.1
36030	0.01	-	0.8

Certified by *Dennis Chonty*

WELSH.



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

Assay Certificate

7W-2548-RA1

Company: **OPAWICA EXPLORATIONS INC.**
Project:
Attn: F. Sharpley

Date: AUG-08-07

We hereby certify the following Assay of 80 Core samples submitted JUL-25-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
36031	0.01	-	0.4
36032	0.01	-	0.4
36033	0.01	0.01	0.2
36034	0.01	-	0.3
36035	0.01	-	0.1
36036	0.01	-	0.2
36037	0.14	-	0.2
36038	0.01	-	0.3
36039	0.03	-	0.4
36040	0.01	-	0.3
36041	0.07	-	0.5
36042	0.02	-	0.1
36043	0.01	-	0.1
36044	0.01	-	0.1
36045	0.60	-	0.9
36046	0.03	-	0.1
36047	0.02	0.01	0.1
36048	0.01	-	0.1
36049	0.02	-	0.1
36050	0.03	-	0.1
Blank	0.01	-	-
STD OxK48	3.48	-	-

Certified by Dennis Chant



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

Assay Certificate

7W-2696-RA1

Company: **OPAWICA RESOURCES INC.**

Date: AUG-21-07

Project:

Attn: F. Sharpley

WALKER

We hereby certify the following Assay of 74 Core samples submitted AUG-07-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
36051	0.01	-	0.1
36052	0.01	-	0.1
36053	0.01	-	0.2
36054	0.01	-	0.1
36055	0.01	-	0.1
36056	0.01	-	0.2
36057	0.01	-	0.1
36058	0.01	-	0.1
36059	0.01	0.01	0.1
36060	0.01	-	0.1
36061	0.01	-	0.2
36062	0.01	-	0.1
36063	0.01	-	0.2
36064	0.01	-	0.2
36065	1.82	-	33.6
36066	0.01	-	0.2
36067	0.01	-	0.1
36068	0.01	-	0.1
36069	0.03	0.02	0.2
36070	0.01	-	0.2
36071	0.01	-	0.1
36072	0.01	-	0.1
36073	0.01	-	0.2
36074	0.01	-	0.1
36075	0.01	-	0.1
36076	0.01	-	0.2
36077	0.01	-	0.2
36078	0.01	-	0.1
36079	0.01	-	0.3
36080	0.02	0.03	0.3

Certified by *Dennis Chantley*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

Assay Certificate

7W-2696-RA1

Company: **OPAWICA RESOURCES INC.**

Date: AUG-21-07

Project:

Attn: F. Sharpley

WALKER

We hereby certify the following Assay of 74 Core samples submitted AUG-07-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
36081	0.01	-	0.2
36082	0.01	-	0.1
36083	0.01	-	0.3
36084	0.01	-	0.1
36085	4.18	-	1.1
36086	0.01	-	0.2
36087	0.01	-	0.1
36088	0.02	-	0.3
36089	0.02	-	0.2
36090	0.05	-	0.1
36091	0.04	-	0.1
36092	0.01	-	0.1
36093	0.05	-	0.1
36094	0.05	-	0.1
36095	0.01	-	0.1
36096	0.01	-	0.1
36097	0.01	-	0.1
36098	0.01	0.01	0.2
36099	0.01	-	0.1
36100	0.01	-	0.2
36101	0.01	-	0.1
36102	0.01	-	0.1
36103	0.01	-	0.1
36104	0.01	-	0.1
36105	0.01	-	0.1
36106	0.01	-	0.1
36107	0.01	-	0.1
36108	0.01	-	0.1
36109	0.01	0.01	0.1
36110	0.01	-	0.1

Certified by *Dennis Chantre*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

Assay Certificate

7W-2696-RA1

Company: **OPAWICA RESOURCES INC.**

Date: AUG-21-07

Project:

Attn: F. Sharpley

WALKER

We hereby certify the following Assay of 74 Core samples submitted AUG-07-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
36111	0.01	-	0.1
36112	0.01	-	0.1
36113	0.01	-	0.1
36114	0.55	-	1.5
36115	0.01	-	0.2
36116	0.01	0.01	0.1
36117	0.01	-	0.2
36118	0.01	-	0.1
36119	0.01	-	0.1
36120	0.01	-	0.2
36121	0.01	-	0.1
36122	0.03	-	0.2
36123	0.02	-	0.2
36124	0.01	0.01	0.1
Blank	0.01	-	-
STD OxK48	3.63	-	-

Certified by *Dennis Christie*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

WALKER

Page 1 of 3

7W-2697-RA1

Date: AUG-17-07

Assay Certificate

Company: **OPAWICA RESOURCES INC.**
Project:
Attn: F. Sharpley

We hereby certify the following Assay of 74 Core samples submitted AUG-07-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
36125	0.01	-	0.1
36126	0.01	-	0.1
36127	0.02	-	0.1
36128	0.01	-	0.2
36129	0.01	-	0.1
36130	0.01	0.01	0.2
36131	0.01	-	0.2
36132	0.01	-	0.3
36133	0.01	-	0.4
36134	2.73	-	0.1
36135	0.01	-	0.4
36136	0.01	-	0.7
36137	0.01	-	0.3
36138	0.01	-	0.1
36139	0.01	-	0.1
36140	0.01	-	0.2
36141	0.01	0.01	0.1
36142	0.01	-	0.1
36143	0.01	-	0.2
36144	0.01	-	0.1
36145	0.02	-	0.1
36146	0.01	-	0.1
36147	0.01	-	0.2
36148	0.01	-	0.4
36149	0.01	-	0.1
36150	0.01	0.01	0.1
36151	0.01	-	0.2
36152	0.01	-	0.2
36153	0.04	-	0.2
36154	0.58	-	0.9

Certified by Doris Charley

1 Cameron Ave., P.O. Box 10, Swastika, Ontario P0K 1T0
Telephone (705) 642-3244 Fax (705) 642-3300



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

WALKER

Page 2 of 3

Assay Certificate

7W-2697-RA1

Company: **OPAWICA RESOURCES INC.**

Date: AUG-17-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 74 Core samples submitted AUG-07-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
36155	0.01	-	0.1
36156	0.01	-	0.1
36157	0.02	-	0.2
36158	0.01	-	0.1
36159	0.01	-	0.1
36160	0.01	-	0.1
36161	0.01	-	0.3
36162	0.01	-	0.2
36163	0.01	-	0.2
36164	0.01	-	0.1
36165	0.03	0.01	0.2
36166	0.01	-	0.2
36167	0.01	-	0.2
36168	0.01	-	0.2
36169	0.01	-	0.1
36170	0.01	-	0.1
36171	0.01	-	0.1
36172	0.01	-	0.1
36173	0.02	-	0.1
36174	1.75	-	33.3
36175	0.03	-	0.1
36176	0.01	0.02	0.5
36177	0.01	-	0.3
36178	0.01	-	0.3
36179	0.01	-	0.3
36180	0.01	-	0.1
36181	0.21	-	1.5
36182	0.01	0.01	0.2
36183	0.01	-	0.2
36184	0.04	-	0.1

Certified by Doris Chantre



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

WALKER/WELSH

Page 3 of 3

7W-2697-RA1

Date: AUG-17-07

Assay Certificate

Company: OPAWICA RESOURCES INC.

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 74 Core samples submitted AUG-07-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
36185	0.01	-	0.1
36186	0.01	0.01	0.1
36187	0.01	-	0.2
36188	0.01	-	0.4
36189	0.01	-	0.1
36190	0.01	-	0.1
36191	0.01	-	0.7
36192	0.01	-	0.3
36193	0.01	-	0.4
36194	4.00	-	1.4
36195	0.01	-	0.4
36196	0.01	0.01	0.3
36197	0.01	-	0.2
36198	0.01	-	0.2
Blank	0.01	-	-
STD OXK48	3.52	-	-

62/74
WALKER (84%)

12/74
WELSH (16%)

Certified by Dennis Chast

1 Cameron Ave., P.O. Box 10, Swastika, Ontario P0K 1T0
Telephone (705) 642-3244 Fax (705) 642-3300



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

7W-2698-RA1

Company: **OPAWICA RESOURCES INC.**

Date: AUG-21-07

Project:

Attn: F. Sharpley

WFSH

We hereby certify the following Assay of 48 Core samples submitted AUG-07-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM
36199	0.01		0.2	164
36200	0.02		0.2	75
36201	0.01	0.02	0.2	71
36202	0.01		0.5	100
36203	0.01		0.4	111
36204	0.01		0.1	10
36205	0.01		0.1	52
36206	0.01		0.2	69
36207	0.01		0.1	141
36208	0.03		0.2	136
36209	0.01		0.1	108
36210	0.02		0.2	92
36211	0.01		0.1	85
36212	0.01	0.01	0.1	60
36213	0.01		0.2	62
36214	0.61		1.5	5200
36215	0.01		0.2	75
36216	0.01		0.1	48
36217	0.01		0.2	93
36218	0.01		0.1	108
36219	0.01		0.1	147
36220	0.01		0.2	115
36221	0.01		0.1	108
36222	0.01	0.01	0.2	224
36223	0.01		0.2	232
36224	0.01		0.1	10
36225	0.01		0.3	389
36226	0.02		0.1	68
36227	0.02		0.3	33
36228	0.01		0.1	21

Certified by *Denis Charley*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

7W-2698-RA1

Company: OPAWICA RESOURCES INC.

Date: AUG-21-07

Project:

Attn: F. Sharpley

WGLSH

We hereby certify the following Assay of 48 Core samples submitted AUG-07-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM
36229	0.01		0.1	77
36230	0.01		0.1	49
36231	0.02		0.1	87
36232	0.01		0.1	80
36233	0.02	0.01	0.1	43
36234	2.77		0.1	113
36235	0.01		0.2	53
36236	0.01		0.3	32
36237	0.01		0.5	56
36238	0.01		0.2	33
36239	0.02		0.2	42
36240	0.02		0.4	39
36241	0.01	0.01	0.3	43
36242	0.01		0.4	61
36243	0.01		0.3	59
36244	0.01		0.1	11
36245	0.01		0.4	38
36246	0.01		0.1	43
Blank	0.01		-	-
STD OxK48	3.57		-	-

Certified by Dennis Christy



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

7W-2699-RA1

Date: AUG-22-07

Assay Certificate

Company: **OPAWICA RESOURCES INC.**


Project:

Attn: F. Sharpley

WGS#

We hereby certify the following Assay of 54 Core samples submitted AUG-07-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
36247	0.10	0.07	0.2
36248	0.03	-	0.1
36249	0.01	-	0.1
36250	0.01	-	0.1
36251	0.01	-	0.1
36252	0.10	0.09	0.1
36253	0.01	-	0.1
36254	0.60	-	0.9
36255	0.08	-	0.1
36256	0.01	-	0.1
36257	0.01	-	0.1
36258	0.01	-	0.1
36259	0.01	-	0.1
36260	0.01	-	0.1
36261	0.01	-	0.1
36262	0.01	-	0.1
36263	0.04	-	0.4
36264	0.03	-	0.4
36265	0.01	-	0.1
36266	0.01	-	0.1
36267	0.01	-	0.1
36268	0.01	-	0.1
36269	0.01	-	0.1
36270	0.01	-	0.1
36271	0.01	-	0.1
36272	0.01	-	0.1
36273	0.01	-	0.1
36274	0.01	-	0.1
36275	1.79	-	33.0
36276	0.01	-	0.1

Certified by 



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

7W-2699-RA1

Date: AUG-22-07

WBSH

Assay Certificate

Company: **OPAWICA RESOURCES INC.**
Project:
Attn: F. Sharpley

We hereby certify the following Assay of 54 Core samples submitted AUG-07-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
36277	0.01	-	0.2
36278	0.01	-	0.1
36279	0.01	-	0.1
36280	0.01	-	0.1
36281	0.01	-	0.2
36282	0.01	0.01	0.1
36283	0.01	-	0.3
36284	0.01	-	0.4
36285	0.01	-	0.1
36286	0.01	-	0.1
36287	0.01	-	0.2
36288	0.02	-	0.3
36289	0.02	-	0.1
36290	0.01	0.01	0.1
36291	0.01	-	0.1
36292	0.02	-	0.1
36293	0.01	-	0.1
36294	0.01	-	0.1
36295	4.15	-	1.0
36296	0.01	-	0.2
36297	0.01	-	0.1
36298	0.01	-	0.1
36299	0.01	-	0.2
36300	0.01	-	0.3
Blank	0.01	-	-
STD OxK48	3.57	-	-

Certified by *Dennis Chantre*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

7W-2700-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Project:

Attn: F. Sharpley

Date: AUG-22-07

WELS H

We hereby certify the following Assay of 55 Core samples submitted AUG-07-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
36301	0.04	-	0.1
36302	0.01	-	0.1
36303	0.01	-	0.1
36304	0.01	-	0.1
36305	0.01	-	0.1
36306	0.01	-	0.5
36307	0.03	0.04	1.2
36308	0.01	-	0.4
36309	0.01	-	0.2
36310	0.01	-	0.4
36311	0.01	-	0.3
36312	0.01	-	0.2
36313	0.01	-	0.2
36314	0.01	-	0.1
36315	0.62	-	1.5
36316	0.01	-	0.2
36317	0.01	-	0.1
36318	0.01	0.01	0.2
36319	0.01	-	0.1
36320	0.01	-	0.9
36321	0.01	-	0.1
36322	0.02	-	0.1
36323	0.01	-	0.1
36324	0.01	-	0.2
36325	0.01	-	0.1
36326	0.01	-	1.6
36327	0.02	0.01	1.8
36328	0.18	-	6.9
36329	2.38	2.47	8.5
36330	3.10	3.07	2.1

Certified by *Denis Chorty*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

7W-2700-RA1

Date: AUG-22-07

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Project:

Attn: F. Sharpley

W025H

We hereby certify the following Assay of 55 Core samples submitted AUG-07-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
36331	0.01	-	0.4
36332	0.01	-	0.1
36333	0.24	0.27	1.1
36334	0.01	-	0.1
36335	2.74	-	0.1
36336	0.01	-	0.1
36337	0.01	-	0.1
36338	0.03	-	0.1
36339	0.02	-	0.3
36340	0.01	0.02	0.3
36341	0.01	-	1.0
36342	0.01	-	0.1
36343	0.02	-	0.1
36344	0.01	-	0.1
36345	0.01	-	0.1
36346	0.01	-	0.1
36347	0.01	-	0.1
36348	0.02	-	0.5
36349	0.03	-	1.2
36350	0.03	0.03	1.3
36351	0.01	-	1.1
36352	0.01	-	0.2
36353	0.01	-	0.1
36354	0.02	-	0.2
36355	0.59	-	0.8
Blank	0.01	-	-
STD OxK48	3.59	-	-

Certified by *Dennis Chantre*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

7W-2701-RA1

Company: OPAWICA RESOURCES INC.

Date: AUG-22-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 55 Core samples submitted AUG-07-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
36356	0.05	0.01	1.4
36357	0.01	-	0.3
36358	0.14	-	0.3
36359	0.04	-	0.3
36360	0.05	-	0.2
36361	0.01	-	0.1
36362	0.01	-	0.1
36363	0.02	-	0.1
36364	0.02	-	0.1
36365	0.01	-	0.1
36366	0.01	-	0.2
36367	0.01	0.01	0.1
36368	0.01	-	0.1
36369	0.01	-	0.2
36370	0.64	-	1.6
36371	0.01	-	0.1
36372	0.01	-	0.1
36373	0.01	-	0.1
36374	0.01	-	0.1
36375	0.01	-	0.1
36376	0.01	-	0.2
36377	0.01	-	0.1
36378	0.01	0.01	0.2
36379	0.01	-	0.2
36380	0.01	-	0.1
36381	0.01	-	0.1
36382	0.01	-	0.2
36383	0.01	-	0.2
36384	0.01	-	0.1
36385	0.01	-	0.1

WGLSH

WALKER

Certified by *Denis Chonty*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

7W-2701-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Date: AUG-22-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 55 Core samples submitted AUG-07-07 by .

WALKER

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
36386	0.01	-	0.1
36387	0.01	-	0.1
36388	0.01	0.01	0.1
36389	0.01	-	0.1
36390	2.75	-	0.1
36391	0.01	-	0.1
36392	0.01	-	0.1
36393	0.01	-	0.3
36394	0.01	-	0.4
36395	0.03	-	3.3
36396	0.01	-	4.9
36397	0.01	-	3.3
36398	0.01	-	1.9
36399	0.01	-	1.9
36400	0.01	-	0.1
36401	0.01	0.01	0.9
36402	0.01	-	1.5
36403	0.01	-	1.0
36404	0.01	-	0.1
36405	0.01	-	0.1
36406	0.01	-	0.1
36407	0.01	-	0.3
36408	0.01	-	0.3
36409	0.03	0.01	0.4
36410	0.60	-	-
Blank	0.01	-	-
STD OxK48	3.59	-	-

Certified by *Denis Chrotes*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

7W-2702-RA1

Company: **OPAWICA RESOURCES INC.**

Date: AUG-22-07

Project:

Attn: F. Sharpley

WAUKER

We hereby certify the following Assay of 55 Core samples submitted AUG-07-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
36411	0.02	-	0.3
36412	0.01	-	0.3
36413	0.01	-	0.2
36414	0.01	0.01	0.1
36415	0.01	-	0.1
36416	0.01	-	0.1
36417	0.01	-	0.1
36418	0.01	-	0.1
36419	0.01	-	0.1
36420	0.01	-	0.1
36421	0.01	-	0.1
36422	0.01	-	0.1
36423	0.01	0.01	0.1
36424	0.01	-	0.1
36425	0.01	-	0.8
36426	0.01	-	1.9
36427	0.01	-	1.6
36428	0.01	-	0.1
36429	0.01	-	0.1
36430	1.83	-	32.7
36431	0.01	-	0.3
36432	0.01	-	0.4
36433	0.01	0.01	0.7
36434	0.01	-	1.9
36435	0.01	-	0.8
36436	0.01	-	1.7
36437	0.01	-	0.7
36438	0.01	-	0.3
36439	0.01	-	0.4
36440	0.01	-	0.1

Certified by *Dennis Chant*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

7W-2702-RA1

Company: **OPAWICA RESOURCES INC.**
Project:
Attn: F. Sharpley

Date: AUG-22-07

We hereby certify the following Assay of 55 Core samples submitted AUG-07-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
36441	0.01	-	0.3
36442	0.02	-	0.1
36443	0.02	-	0.1
36444	0.01	-	0.1
36445	0.01	-	0.6
36446	0.02	-	0.8
36447	0.01	0.01	0.5
36448	0.01	-	0.7
36449	0.01	-	0.1
36450	4.05	-	1.0
36451	0.01	-	0.1
36452	0.01	-	0.1
36453	0.01	-	0.3
36454	0.02	-	0.1
36455	0.01	-	0.1
36456	0.01	0.01	0.1
36457	0.01	-	0.1
36458	0.01	-	0.1
36459	0.01	-	0.1
36460	0.01	-	0.1
36461	0.01	-	0.1
36462	0.01	-	0.1
36463	0.01	-	0.1
36464	0.01	-	0.2
36465	0.01	-	0.3
Blank	0.01	-	-
STD OxK48	3.57	-	-

Certified by

1 Cameron Ave., P.O. Box 10, Swastika, Ontario P0K 1T0
Telephone (705) 642-3244 Fax (705) 642-3300



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Assay Certificate

7W-2703-RA1

Company: OPAWICA RESOURCES INC.

Project:

Attn: F. Sharpley

Date: AUG-22-07

WALKER

We hereby certify the following Assay of 25 Core samples submitted AUG-07-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
36466	0.02	0.07	0.2
36467	0.01	-	0.1
36468	0.03	-	0.2
36469	0.02	-	0.1
36470	0.62	-	1.5
36471	0.01	-	0.2
36472	0.01	-	0.1
36473	0.01	-	0.2
36474	0.01	-	0.4
36475	0.01	-	0.4
36476	0.01	-	0.3
36477	0.01	-	0.1
36478	0.01	-	0.1
36479	0.01	-	0.2
36480	0.01	-	0.1
36481	0.01	0.01	0.2
36482	0.01	-	0.2
36483	0.01	-	0.4
36484	0.01	-	0.1
36485	0.16	-	0.3
36486	0.16	-	0.4
36487	0.07	-	0.3
36488	0.03	-	0.3
36489	0.03	-	0.3
36490	0.01	0.01	0.2
Blank	0.01	-	-
STD OxK48	3.55	-	-

Certified by

1 Cameron Ave., P.O. Box 10, Swastika, Ontario P0K 1T0
Telephone (705) 642-3244 Fax (705) 642-3300



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

7W-2769-RA1

Assay Certificate

Company: **OPAWICA EXPLORATIONS INC.**

Project:

Attn: F. Sharpley

Date: AUG-27-07

CAM KING

We hereby certify the following Assay of 60 Core samples submitted AUG-13-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
36491	0.46	0.38	0.4
36492	0.01	-	0.1
36493	0.21	-	0.3
36494	2.75	-	0.1
36495	0.01	-	0.2
36496	0.01	-	0.1
36497	0.01	-	0.1
36498	0.01	-	0.2
36499	0.01	-	0.1
36500	0.12	-	0.1
36501	0.10	-	0.1
36502	0.11	-	0.1
36503	0.08	-	0.2
36504	0.11	-	0.4
36505	0.54	0.44	1.1
36506	0.60	-	0.7
36507	0.08	-	0.1
36508	0.01	-	0.1
36509	0.01	-	0.1
36510	0.01	-	0.1
36511	0.01	-	0.1
36512	0.01	-	0.1
36513	0.01	-	0.1
36514	0.02	-	0.1
36515	0.02	-	0.1
36516	0.01	-	0.1
36517	0.01	-	0.1
36518	0.01	-	0.1
36519	0.01	-	0.1
36520	0.01	0.01	0.1

Certified by *Dennis Christie*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

7W-2769-RA1

Assay Certificate

Company: OPAWICA EXPLORATIONS INC.

Project:

Attn: F. Sharpley

Date: AUG-27-07

CAMKING

We hereby certify the following Assay of 60 Core samples submitted AUG-13-07 by :

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
36521	0.02	-	0.1
36522	0.01	-	0.1
36523	0.01	-	0.1
36524	0.01	-	0.1
36525	0.01	-	0.1
36526	1.73	-	33.7
36527	0.01	-	0.1
36528	0.01	-	0.2
36529	0.17	-	0.3
36530	0.19	0.17	0.4
36531	0.01	-	0.2
36532	0.01	-	0.1
36533	0.02	-	0.3
36534	0.03	-	0.7
36535	0.04	-	0.7
36536	0.01	-	0.1
36537	0.18	-	1.3
36538	0.05	-	1.2
36539	0.01	-	1.5
36540	0.16	-	1.3
36541	0.62	0.71	4.0
36542	0.01	-	0.5
36543	0.18	-	0.6
36544	0.09	-	0.4
36545	0.10	-	0.1
36546	4.01	-	1.0
36547	0.12	-	0.4
36548	0.01	-	0.1
36549	0.01	-	0.1
36550	0.01	-	0.2

Certified by *Dennis Chant*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

Assay Certificate

7W-2769-RA1

Company: OPAWICA EXPLORATIONS INC.

Date: AUG-27-07

Project:

Attn: F. Sharpley

CAM KING

We hereby certify the following Assay of 60 Core samples submitted AUG-13-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
Blank	0.01	-	-
STD OxK48	3.64	-	-

Certified by *Dennis Chantre*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

7W-2770-RA1

Assay Certificate

Company: **OPAWICA EXPLORATIONS INC.**

Date: AUG-27-07

Project:

Attn: F. Sharpley

Chinking

We hereby certify the following Assay of 74 Core samples submitted AUG-13-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM
36551	0.01	-	0.1	178
36552	0.08	-	0.1	13
36553	0.11	-	0.2	9
36554	0.26	-	0.1	11
36555	0.26	-	0.1	13
36556	0.01	-	0.1	11
36557	0.05	-	0.1	8
36558	0.03	0.01	0.1	6
36559	0.01	-	0.1	11
36560	0.01	-	0.1	11
36561	0.01	-	0.1	-
36562	0.01	-	0.2	-
36563	0.01	-	0.1	-
36564	0.01	-	0.1	-
36565	0.01	-	0.1	-
36566	0.63	-	1.6	-
36567	0.01	-	0.1	-
36568	0.01	-	0.1	-
36569	0.01	0.01	0.3	67
36570	0.02	-	0.4	714
36571	0.01	-	0.1	11
36572	0.01	-	0.1	-
36573	0.01	-	0.1	-
36574	0.02	-	0.1	-
36575	0.01	-	0.1	-
36576	0.01	-	0.1	-
36577	0.02	-	0.1	-
36578	0.03	-	0.1	-
36579	0.01	-	0.1	-
36580	0.02	-	0.1	-

Certified by *Dennis Chantre*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

Assay Certificate

7W-2770-RA1

Company: **OPAWICA EXPLORATIONS INC.**

Date: AUG-27-07

Project:

Attn: F. Sharpley

CRAM KING

We hereby certify the following Assay of 74 Core samples submitted AUG-13-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM
36581	0.02	0.01	0.1	-
36582	0.01	-	0.1	-
36583	0.01	-	0.1	-
36584	0.14	-	0.1	-
36585	0.01	-	0.1	-
36586	2.71	-	0.1	-
36587	0.01	-	0.1	-
36588	0.01	-	0.1	-
36589	0.01	-	0.1	-
36590	0.01	-	0.1	-
36591	0.01	-	0.1	-
36592	0.01	0.01	0.1	-
36593	0.01	-	0.1	-
36594	0.03	-	0.1	-
36595	0.01	-	0.1	-
36596	0.01	-	0.1	-
36597	0.03	-	0.1	-
36598	0.01	-	0.1	-
36599	0.18	-	0.2	-
36600	0.01	-	0.3	-
36601	0.22	-	0.1	-
36602	0.04	0.03	0.1	-
36603	0.14	-	0.2	-
36604	0.01	-	0.3	-
36605	0.01	-	0.4	-
36606	0.58	-	0.8	-
36607	0.01	-	0.2	-
36608	0.04	-	0.1	-
36609	0.05	-	0.2	-
36610	0.28	0.31	2.0	-

Certified by *Dennis Chate*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

7W-2770-RA1

Date: AUG-27-07

Assay Certificate

Company: **OPAWICA EXPLORATIONS INC.**

Project:

Attn: F. Sharpley

Cum King

We hereby certify the following Assay of 74 Core samples submitted AUG-13-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM
36611	0.24	-	1.5	-
36612	0.01	-	0.2	-
36613	0.01	-	0.3	-
36614	0.01	-	0.3	-
36615	0.01	-	0.2	-
36616	0.01	-	0.1	-
36617	0.01	0.01	0.2	-
36618	0.01	-	0.3	-
36619	0.01	-	0.2	-
36620	0.01	-	0.3	-
36621	0.01	-	0.2	-
36622	0.01	-	0.1	-
36623	0.01	-	0.2	-
36624	0.01	0.01	0.1	-
Blank	0.01	-	-	-
STD OxK48	3.48	-	-	-

Certified by *Dennis Chait*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Starwille

Page 1 of 3

Assay Certificate

7W-2771-RA1

Company: **OPAWICA EXPLORATIONS INC.**

Date: AUG-29-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 75 Core samples submitted AUG-13-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM
36625	0.01	-	0.3	107
36626	1.78	-	33.2	7
36627	0.02	-	0.3	70
36628	0.01	-	0.2	31
36629	0.14	0.13	0.4	58
36630	0.09	-	0.3	71
36631	0.13	-	0.1	73
36632	0.03	-	0.2	53
36633	0.01	-	0.3	51
36634	0.01	-	0.3	73
36635	0.01	-	0.3	81
36636	0.01	-	0.1	10
36637	0.45	-	1.0	55
36638	0.38	-	0.6	68
36639	0.31	-	0.5	73
36640	0.03	-	0.2	83
36641	0.29	0.28	0.7	74
36642	0.15	-	0.5	78
36643	0.01	-	0.3	88
36644	0.01	-	0.2	69
36645	0.02	-	0.3	83
36646	4.18	-	0.9	8
36647	0.01	-	0.4	173
36648	0.03	-	0.4	60
36649	0.47	0.28	0.3	62
36650	0.28	-	0.6	90
36651	0.02	0.01	0.3	41
36652	0.01	-	0.2	41
36653	0.01	-	0.2	62
36654	0.01	-	0.2	47

Certified by *Dennis Christy*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Stamundk

Page 2 of 3

Assay Certificate

7W-2771-RA1

Company: **OPAWICA EXPLORATIONS INC.**

Date: AUG-29-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 75 Core samples submitted AUG-13-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM
36655 ✓	0.01	-	0.3	45
36656	0.01	-	0.1	9
36657	0.04	-	0.6	65
36658	0.11	-	0.5	36
36659	0.01	-	0.3	44
36660	0.05	-	0.4	61
36661	0.01	-	0.2	41
36662	0.11	-	0.2	58
36663	0.13	-	0.4	75
36664	0.04	0.01	0.3	66
36665	0.01	-	0.1	59
36666	0.61	-	1.5	5200
36667	0.01	-	0.5	95
36668	0.04	-	0.3	79
36669	0.01	-	0.4	48
36670	0.10	-	0.7	47
36671	0.14	-	0.7	63
36672	0.01	-	0.2	71
36673	0.01	-	0.4	69
36674	0.01	-	0.3	36
36675	0.01	-	0.2	36
36676	0.01	-	0.1	8
36677	0.01	0.03	0.1	43
36678	0.22	-	0.7	37
36679	0.04	-	0.5	80
36680	0.01	-	0.1	63
36681	0.04	-	0.1	54
36682	0.01	-	0.1	54
36683	0.01	-	0.2	53
36684	0.07	-	0.2	49

Certified by *Dennis Chantz*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

54mmol

Page 3 of 3

7W-2771-RA1

Assay Certificate

Company: **OPAWICA EXPLORATIONS INC.**

Date: AUG-29-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 75 Core samples submitted AUG-13-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM
36685	0.06	-	0.3	55
36686	2.84	-	0.1	112
36687	0.04	-	0.2	51
36688	0.05	0.05	0.3	102
36689	0.08	-	0.6	104
36690	0.07	-	0.3	85
36691	0.20	-	0.4	55
36692	0.19	-	0.3	27
36693	0.05	-	0.7	33
36694	0.01	-	0.2	47
36695	0.01	-	0.2	185
36696	0.01	-	0.2	186
36697	0.01	-	0.1	10
36698	0.01	-	0.1	118
36699	0.01	0.01	0.1	76
Blank	0.01	-	-	-
STD OxK48	3.56	-	-	-

Certified by *Dennis Christ*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

7W-2772-RA1

Date: AUG-29-07

Assay Certificate

Company: **OPAWICA EXPLORATIONS INC.**

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 81 Core samples submitted AUG-17-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
36700	0.01	-	0.1
36701	0.01	-	0.1
36702	0.01	-	0.2
36703	0.01	-	0.1
36704	0.01	-	0.1
36705	0.02	-	0.1
36706	0.14	-	0.1
36707	0.60	-	1.0
36708	0.03	-	0.2
36709	0.01	-	0.1
36710	0.01	-	0.1
36711	0.01	-	0.1
36712	0.01	-	0.1
36713	0.01	0.01	0.1
36714	0.01	-	0.1
36715	0.01	-	0.1
36716	0.01	-	0.1
36717	0.01	-	0.1
36718	0.01	-	0.1
36719	0.01	-	0.1
36720	0.01	-	0.1
36721	0.01	-	0.1
36722	0.01	-	0.1
36723	0.01	-	0.1
36724	0.01	-	0.1
36725	0.03	-	0.4
36726	0.03	-	0.1
36727	0.05	-	0.3
36728	0.04	-	0.4
36729	0.07	0.07	0.4

Certified by *Dennis Christie*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

7W-2772-RA1

Date: AUG-29-07

Assay Certificate

Company: **OPAWICA EXPLORATIONS INC.**

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 81 Core samples submitted AUG-17-07 by .

Combing

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
36730	1.80	-	33.9
36731	0.90	0.89	0.5
36732	0.10	-	0.3
36733	0.22	-	0.3
36734	0.46	0.45	0.1
36735	0.13	-	0.4
36736	0.46	0.43	0.5
36737	0.07	-	0.4
36738	0.03	-	0.4
36739	0.02	-	0.4
36740	0.01	-	0.1
36741	0.17	-	0.5
36742	0.07	-	0.4
36743	0.03	-	0.3
36744	0.15	-	0.3
36745	0.01	-	0.6
36746	0.11	-	0.5
36747	0.01	-	0.8
36748	0.01	-	0.4
36749	0.01	-	0.3
36750	4.04	-	1.1
36751	0.01	-	0.2
36752	0.06	-	0.4
36753	0.01	-	0.3
36754	0.03	-	0.3
36755	0.01	-	0.3
36756	0.09	0.09	0.4
36757	0.04	-	0.4
36758	0.05	-	0.4
36759	0.05	-	0.4

Certified by *Janis Chant*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

7W-2772-RA1

Date: AUG-29-07

Assay Certificate

Company: **OPAWICA EXPLORATIONS INC.**

Project:

Attn: (F. Sharpley

We hereby certify the following Assay of 81 Core samples submitted AUG-17-07 by .

Cumkiny

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
36760	0.01	-	0.1
36761	0.05	-	0.4
36762	0.01	-	0.3
36763	0.01	-	0.3
36764	0.01	-	0.2
36765	0.10	-	0.4
36766	0.79	1.00	0.4
36767	0.19	-	0.3
36768	0.08	-	0.1
36769	0.12	-	0.1
36770	0.62	-	1.8
36771	0.19	-	0.3
36772	0.01	-	0.1
36773	0.03	-	0.2
36774	0.01	-	0.2
36775	0.14	-	0.1
36776	0.10	-	0.6
36777	0.05	-	0.5
36778	0.04	0.03	0.2
36779	0.06	-	0.2
36780	0.01	-	0.1
Blank	0.01	-	-
STD OxK48	3.57	-	-

Certified by *Dennis Chabry*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

7W-2829-RA1

Company: **OPAWICA RESOURCES INC.**

Date: SEP-04-07

Project:

Attn: F. Sharpley

Walter Campbell

We hereby certify the following Assay of 56 Core samples submitted AUG-21-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
36781	0.03	-	0.1
36782	0.01	-	0.1
36783	0.03	0.01	0.1
36784	0.02	-	0.1
36785	0.04	-	0.1
36786	0.01	-	0.1
36787	0.01	-	0.1
36788	0.03	-	0.1
36789	0.01	-	0.1
36790	2.75	-	0.1
36791	0.02	-	0.1
36792	0.04	-	0.1
36793	0.03	-	0.1
36794	0.07	-	0.2
36795	0.02	-	0.1
36796	0.01	-	0.1
36797	0.02	0.01	0.2
36798	0.04	-	0.2
36799	0.03	-	0.2
36800	0.01	-	0.1
36801	0.01	-	0.1
36802	0.01	-	0.1
36803	0.03	-	0.1
36804	0.02	-	0.1
36805	0.08	-	0.8
36806	0.02	-	0.6
36807	0.12	-	0.7
36808	0.29	0.29	1.8
36809	0.11	-	0.7
36810	0.21	-	0.7

Certified by *Dennis Clark*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

7W-2829-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Date: SEP-04-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 56 Core samples submitted AUG-21-07 by .

~~detrital~~ *Sampling*

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
36811	1.78	1.78	6.6
36812	0.06	-	0.5
36813	0.03	-	0.1
36814	0.64	-	1.5
36815	0.03	-	0.1
36816	0.01	-	0.1
36817	0.02	-	0.1
36818	0.02	-	0.2
36819	0.03	-	0.3
36820	0.04	-	0.3
36821	0.01	-	0.1
36822	0.01	-	0.1
36823	0.01	-	0.2
36824	0.01	-	0.1
36825	0.01	-	0.4
36826	0.54	0.51	1.4
36827	0.08	-	0.3
36828	0.23	-	1.1
36829	0.01	-	0.8
36830	0.01	-	0.5
36831	0.01	-	0.4
36832	0.03	-	0.5
36833	0.01	-	0.3
36834	2.79	-	0.1
36835	0.01	-	0.6
36836	0.01	0.01	0.7
Blank	0.01	-	-
STD OxK48	3.52	-	-

Certified by *Denis Chank*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

Assay Certificate

(Cannking)

7W-2830-RA1

Company: **OPAWICA RESOURCES INC.**

Date: SEP-11-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 63 Core samples submitted AUG-21-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM
36837	0.04	-	0.3	-
36838	0.03	-	0.6	-
36839	0.04	-	0.4	-
36840	0.07	-	0.3	-
36841	0.11	-	0.4	-
36842	0.08	0.12	0.4	-
36843	0.12	-	0.3	-
36844	0.01	-	0.1	-
36845	0.03	-	0.1	-
36846	0.37	-	1.7	-
36847	0.29	-	1.6	-
36848	0.10	-	0.4	-
36849	0.09	-	0.5	-
36850	0.54	-	1.8	-
36851	0.14	-	0.5	-
36852	0.23	-	0.2	-
36853	0.07	-	0.3	-
36854	0.62	-	0.8	-
36855	0.01	-	0.7	-
36856	0.04	-	0.2	-
36857	0.05	-	0.5	-
36858	0.15	-	0.4	-
36859	0.05	-	0.3	-
36860	0.03	-	0.3	-
36861	0.03	-	0.2	-
36862	0.02	-	0.5	-
36863	0.01	0.01	0.6	-
36864	0.01	-	0.1	-
36865	0.04	-	0.2	-
36866	0.01	-	0.2	-

Certified by *Dennis Chater*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

Assay Certificate

7W-2830-RA1

Company: **OPAWICA RESOURCES INC.**

Comking

Date: SEP-11-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 63 Core samples submitted AUG-21-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM
36867	2.32	2.60	1.3	600
36868	0.17	-	0.7	968
36869	0.08	-	0.8	332
36870	0.04	-	0.5	844
36871	0.07	-	1.4	589
36872	0.09	-	0.3	510
36873	0.09	-	0.9	631
36874	1.80	-	33.0	7
36875	0.01	-	0.5	509
36876	0.11	-	0.6	452
36877	0.01	-	0.7	159
36878	0.10	-	7.9	3150
36879	0.01	-	0.5	506
36880	0.01	-	0.6	314
36881	0.01	-	0.2	141
36882	0.01	-	0.1	91
36883	0.01	-	0.2	83
36884	0.01	-	0.1	10
36885	0.01	-	0.4	453
36886	0.07	-	0.4	297
36887	0.03	-	0.2	339
36888	0.01	-	0.3	270
36889	0.01	-	1.6	134
36890	0.01	-	0.1	171
36891	0.01	-	0.3	242
36892	0.01	-	0.2	486
36893	0.04	-	0.3	402
36894	0.17	0.14	1.5	1670
36895	0.05	-	0.2	288
36896	4.07	-	1.0	8

Certified by *Dennis Chant*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

Assay Certificate

7W-2830-RA1

Company: **OPAWICA RESOURCES INC.**

Cannery

Date: SEP-11-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 63 Core samples submitted AUG-21-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM
36897	0.04	-	1.5	729
36898	0.01	-	0.1	222
36899	0.01	-	0.1	289
Blank	0.01	-	-	-
STD OxK48	3.59	-	-	-

Certified by *Denis Chantre*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

7W-2831-RA1

Company: **OPAWICA RESOURCES INC.**

Date: SEP-05-07

Project:

Attn: F. Sharpley

Cumulative

We hereby certify the following Assay of 56 Core samples submitted AUG-21-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM	Pb PPM	Zn PPM
44001	0.01	-	0.1	385	1	76
44002	0.07	0.05	0.3	220	10	74
44003	0.08	-	0.3	201	7	70
44004	0.01	-	0.2	86	1	59
44005	0.01	-	0.2	130	1	59
44006	0.03	-	0.4	128	7	55
44007	0.01	-	0.3	73	3	41
44008	0.01	-	0.1	89	1	42
44009	0.01	-	0.3	190	2	43
44010	0.61	-	1.7	5430	13	71
44011	0.01	-	0.3	141	2	49
44012	0.01	-	0.2	82	3	51
44013	0.01	-	0.1	137	7	54
44014	0.01	-	0.3	60	33	60
44015	0.02	-	0.3	86	24	54
44016	0.04	-	0.4	54	33	51
44017	0.01	-	0.4	34	20	45
44018	0.01	0.01	0.3	105	13	43
44019	0.01	-	0.4	96	13	42
44020	0.01	-	0.1	10	1	4
44021	0.05	-	0.2	106	25	45
44022	0.01	-	0.5	174	35	115
44023	0.01	-	0.5	269	18	85
44024	0.01	-	0.5	158	7	51
44025	0.01	-	0.3	125	2	50
44026	0.01	0.02	0.3	128	2	41
44027	0.07	-	0.3	141	13	53
44028	0.02	-	0.3	115	5	51
44029	0.02	-	0.2	133	4	49
44030	2.81	-	0.1	107	18	19

Certified by *Dennis Christie*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

7W-2831-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Date: SEP-05-07

Project:

Attn: F. Sharpley

Camping
~~Stornville~~

We hereby certify the following Assay of 56 Core samples submitted AUG-21-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM	Pb PPM	Zn PPM
44031	0.01	-	0.2	74	4	39
44032	0.01	-	0.2	56	5	56
44033	0.01	-	0.3	164	8	44
44034	0.02	0.01	0.2	93	3	35
44035	0.01	-	0.1	34	8	41
44036	0.05	-	0.2	88	4	35
44037	0.01	-	0.3	140	6	43
44038	0.01	-	0.2	126	3	44
44039	0.01	-	0.2	119	3	47
44040	0.01	-	0.1	10	1	4
44041	0.01	-	0.2	67	4	43
44042	0.05	-	0.3	48	13	83
44043	0.01	0.01	0.3	36	30	103
44044	0.07	-	1.5	59	988	604
44045	0.01	-	0.2	113	29	95
44046	0.01	-	0.2	152	15	85
44047	0.01	-	0.1	171	20	139
44048	0.01	-	0.1	30	15	73
44049	0.13	-	0.4	25	56	163
44050	0.59	-	0.8	13	77	39
44051	0.04	-	0.1	14	15	56
44052	0.15	-	0.3	28	55	67
44053	0.01	-	0.1	9	19	56
44054	0.01	0.01	0.1	31	43	73
44055	0.02	-	0.1	76	87	137
44056	0.01	-	0.1	79	20	216
Blank	0.01	-	-	-	-	-
STD OxK48	3.53	-	-	-	-	-

Certified by *Denis Chantre*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

7W-2832-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Date: SEP-05-07

Project:

Attn: F. Sharpley

*12 - 5/10/07
Camping*

We hereby certify the following Assay of 33 Core samples submitted AUG-21-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM	Pb PPM	Zn PPM
44057	0.01	-	0.3	121	60	273
44058	0.01	-	0.4	171	61	423
44059	0.01	-	0.3	163	57	370
44060	0.01	-	0.1	9	1	5
44061	0.01	0.01	0.1	66	29	108
44062	0.01	-	0.1	20	16	84
44063	0.01	-	0.1	15	21	82
44064	0.02	-	0.4	21	26	83
44065	0.01	-	0.3	316	16	103
44066	0.01	-	0.1	175	4	60
44067	0.01	-	0.1	140	3	63
44068	0.01	-	0.1	63	2	59
44069	0.01	-	0.2	77	25	58
44070	1.91	-	33.5	7	62	25
44071	0.01	-	0.1	59	2	49
44072	0.01	-	0.1	107	7	67
44073	0.01	-	0.1	9	3	43
44074	0.01	0.01	0.1	10	16	72
44075	0.01	-	0.1	155	1	55
44076	0.05	-	0.2	143	14	41
44077	0.04	-	0.4	81	29	41
44078	0.01	-	0.3	92	10	40
44079	0.01	-	0.2	101	7	39
44080	0.01	-	0.1	9	1	4
44081	0.01	-	0.2	237	10	42
44082	0.03	-	0.1	206	3	51
44083	0.08	-	0.3	301	7	42
44084	0.06	-	0.2	166	7	55
44085	0.01	0.01	0.1	142	4	69
44086	0.01	-	0.1	107	1	70

Certified by *Dennis Chroto*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

7W-2832-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Project:

Attn: F. Sharpley

Date: SEP-05-07

comking
[Signature]

We hereby certify the following Assay of 33 Core samples submitted AUG-21-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM	Pb PPM	Zn PPM
44087	0.03	-	0.1	106	1	125
44088	0.06	-	0.1	148	5	64
44089	0.01	0.02	0.1	15	7	54
Blank	0.01	-	-	-	-	-
STD OxK48	3.56	-	-	-	-	-

Certified by *Dennis Chait*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

7W-2833-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Project:

Attn: F. Sharpley

Date: SEP-05-07

Cameron
Stamwood

We hereby certify the following Assay of 58 Core samples submitted AUG-21-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM
44090	4.05	-	0.9	-
44091	0.01	-	0.1	-
44092	0.01	-	0.2	-
44093	0.01	-	0.2	-
44094	0.01	0.01	0.4	-
44095	0.05	-	0.7	-
44096	0.01	-	0.3	-
44097	0.01	-	0.4	-
44098	0.01	-	0.4	-
44099	0.01	-	0.3	-
44100	0.01	-	0.1	-
44101	0.01	-	0.8	-
44102	0.13	-	1.0	-
44103	0.01	-	0.3	371
44104	0.01	-	0.4	406
44105	0.01	-	0.3	245
44106	0.02	-	0.1	183
44107	0.01	-	0.1	-
44108	0.01	-	0.2	-
44109	0.01	-	0.1	-
44110	0.01	-	0.1	-
44111	0.01	-	0.2	-
44112	0.01	-	0.1	-
44113	0.08	-	0.3	-
44114	0.01	-	0.2	-
44115	0.01	0.01	0.1	-
44116	0.61	-	1.7	-
44117	0.01	-	0.2	-
44118	0.01	-	0.2	-
44119	0.01	-	0.1	-

Certified by *Dennis Chate*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

7W-2833-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Date: SEP-05-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 58 Core samples submitted AUG-21-07 by .

Camping

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM
44120	0.01	-	0.1	-
44121	0.01	-	0.1	-
44122	0.01	-	0.1	-
44123	0.01	-	0.1	-
44124	0.01	-	0.1	-
44125	0.01	-	0.1	-
44126	0.01	-	0.1	-
44127	0.01	0.01	0.1	-
44128	0.01	-	0.2	-
44129	0.01	-	0.1	-
44130	0.01	-	0.1	-
44131	0.01	-	0.2	-
44132	0.01	-	0.1	-
44133	0.01	-	0.1	-
44134	0.02	-	0.1	-
44135	0.01	-	0.1	-
44136	2.82	-	0.1	-
44137	0.01	-	0.1	-
44138	0.01	-	0.1	-
44139	0.01	-	0.1	-
44140	0.01	-	0.1	-
44141	0.01	-	0.1	-
44142	0.01	-	0.1	-
44143	0.01	-	0.2	-
44144	0.01	0.01	0.2	-
44145	0.01	-	0.2	-
44146	0.01	-	0.1	-
44147	0.01	-	0.2	-
Blank	0.01	-	-	-
STD OxK48	3.62	-	-	-

Certified by *Dennis Chant*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

7W-2834-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Project:

Attn: F. Sharpley

Date: SEP-05-07

Gamking
~~Swastika~~
17 WELSH
40 GAMKING (70%)
(30%)

We hereby certify the following Assay of 57 Core samples submitted AUG-21-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
44148	0.01	-	0.1
44149	0.01	-	0.3
44150	0.01	0.01	0.2
44151	0.01	-	0.4
44152	0.01	-	0.4
44153	0.01	-	0.2
44154	0.01	-	0.3
44155	0.01	-	0.8
44156	0.60	-	0.8
44157	0.02	-	0.2
44158	0.16	-	0.4
44159	0.73	-	1.4
44160	0.12	0.12	0.3
44161	0.01	-	0.1
44162	0.16	-	0.4
44163	0.15	-	0.1
44164	0.07	-	0.1
44165	0.06	-	0.2
44166	0.01	-	0.1
44167	0.01	-	0.1
44168	0.33	-	0.2
44169	0.18	-	0.4
44170	0.62	0.64	1.1
44171	0.29	-	0.4
44172	0.11	-	0.2
44173	0.01	-	0.3
44174	0.33	-	0.5
44175	0.07	-	0.1
44176	1.79	-	33.7
44177	0.28	-	0.4

Certified by *Dennis Chanty*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

7W-2834-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Project:

Attn: F. Sharpley

Date: SEP-05-07

We hereby certify the following Assay of 57 Core samples submitted AUG-21-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
44178	0.04	-	0.2
44179	0.12	-	0.2
44180	0.28	0.28	1.2
44181	0.06	-	0.4
44182	0.01	-	0.1
44183	0.13	-	0.8
44184	0.09	-	0.2
44185	0.01	-	0.2
44186	0.01	-	0.1
44187	0.01	-	0.1
44188	0.01	-	0.3
44189	0.01	-	0.4
44190	0.01	-	0.1
44191	0.01	-	0.4
44192	0.02	-	1.6
44193	0.01	-	1.0
44194	0.01	-	0.5
44195	0.01	-	0.1
44196	4.05	-	1.0
44197	0.01	-	0.3
44198	0.02	-	1.3
44199	0.01	-	0.4
44200	0.01	0.01	0.5
44201	0.01	-	0.5
44202	0.01	-	0.2
44203	0.01	-	0.3
44204	0.01	-	0.5
Blank	0.01	-	-
STD OxK48	3.56	-	-

Camking

Welsh

Certified by *Dennis Chantre*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

7W-2835-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Date: SEP-05-07

Project:

Attn: F. Sharpley

Welsh

We hereby certify the following Assay of 56 Core samples submitted AUG-21-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
44205	0.01	0.01	0.3
44206	0.01	-	0.1
44207	0.01	-	2.8
44208	0.01	-	2.1
44209	0.01	-	1.8
44210	0.03	-	1.9
44211	0.01	-	1.2
44212	0.01	-	0.9
44213	0.01	-	0.9
44214	0.01	-	0.4
44215	0.01	-	0.2
44216	0.62	-	1.8
44217	0.01	0.01	0.2
44218	0.01	-	0.2
44219	0.01	-	0.3
44220	0.01	-	0.4
44221	0.01	-	0.4
44222	0.01	-	0.1
44223	0.01	-	0.1
44224	0.01	-	0.1
44225	0.01	-	0.1
44226	0.01	-	0.1
44227	0.01	-	0.1
44228	0.01	-	1.2
44229	0.01	0.01	0.9
44230	0.01	-	0.2
44231	0.01	-	0.5
44232	0.01	-	0.1
44233	0.01	-	0.1
44234	0.01	-	0.2

Certified by *Dennis Chant*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

7W-2835-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Project:

Attn: F. Sharpley

Date: SEP-05-07

Welsh

We hereby certify the following Assay of 56 Core samples submitted AUG-21-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
44235	0.01	-	0.4
44236	2.78	-	0.1
44237	0.01	-	0.5
44238	0.01	-	0.2
44239	0.01	-	0.1
44240	0.01	-	0.2
44241	0.01	-	0.2
44242	0.01	0.01	0.2
44243	0.01	-	0.7
44244	0.01	-	0.2
44245	0.01	-	0.1
44246	0.01	-	0.1
44247	0.01	-	0.4
44248	0.01	-	0.1
44249	0.01	-	0.1
44250	0.01	-	0.2
44251	0.01	-	0.1
44252	0.01	-	0.2
44253	0.01	-	0.1
44254	0.01	-	0.1
44255	0.01	-	0.2
44256	0.59	-	0.8
44257	0.01	0.01	0.2
44258	0.01	-	0.4
44259	0.01	-	0.1
44260	0.01	-	0.1
Blank	0.01	-	-
STD OxK48	3.56	-	-

Certified by *Dennis Chant*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

7W-2866-RA1

Assay Certificate

Company: **OPAWICA EXPLORATIONS**

Project:

Attn: F. Sharpley

Date: SEP-13-07

Welsh

We hereby certify the following Assay of 50 Core samples submitted AUG-26-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
36900	0.08	-	0.2
36901	0.01	-	0.1
36902	0.01	-	0.1
36903	0.01	0.01	0.1
36904	0.01	-	0.1
36905	0.01	-	0.1
36906	0.01	-	0.3
36907	0.01	-	0.1
36908	0.01	-	0.1
36909	0.01	0.01	0.1
36910	0.01	-	0.1
36911	0.01	-	0.1
36912	0.01	-	0.2
36913	0.01	-	0.1
36914	0.01	-	0.1
36915	1.71	-	33.6
36916	0.01	-	0.1
36917	0.01	-	0.1
36918	0.01	-	0.1
36919	0.01	-	0.1
36920	0.01	0.01	0.1
36921	0.01	-	0.1
36922	0.01	-	0.1
36923	0.01	-	0.1
36924	0.01	-	0.1
36925	0.01	-	0.1
36926	0.01	-	0.1
36927	0.01	-	0.1
36928	0.01	-	0.1
36929	0.04	-	0.1

Certified by *Dennis Crant*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

7W-2866-RA1

Company: **OPAWICA EXPLORATIONS**

Project:

Attn: F. Sharpley

Welsh

Date: SEP-13-07

We hereby certify the following Assay of 50 Core samples submitted AUG-26-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
36930	0.06	-	0.1
36931	0.34	0.36	0.1
36932	0.01	-	0.1
36933	0.07	-	0.1
36934	0.01	-	0.1
36935	4.07	-	0.7
36936	0.04	-	0.1
36937	0.01	-	0.1
36938	0.02	-	0.1
36939	0.01	-	0.1
36940	0.13	-	0.1
36941	0.01	-	0.1
36942	0.13	-	0.1
36943	0.17	-	0.1
36944	0.11	-	0.1
36945	0.01	-	0.1
36946	0.01	-	0.1
36947	0.96	0.91	0.1
36948	0.34	-	0.1
36949	0.28	-	0.1
Blank	0.01	-	-
STD OxK48	3.61	-	-

Certified by *Dennis Chant*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

7W-2867-RA1

Company: **OPAWICA EXPLORATIONS**

Date: SEP-10-07

Project:

Attn: F. Sharpley

Welsh

We hereby certify the following Assay of 51 Core samples submitted AUG-26-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
36950	0.71	-	0.3
36951	2.21	2.47	0.7
36952	0.89	-	0.3
36953	0.26	-	0.2
36954	1.24	-	0.4
36955	0.59	-	1.5
36956	0.24	-	0.6
36957	0.10	-	0.2
36958	0.39	0.44	0.2
36959	1.41	-	0.5
36960	1.11	-	0.3
36961	0.77	-	0.3
36962	0.09	-	0.3
36963	0.01	-	0.3
36964	0.01	-	0.3
36965	0.01	-	0.1
36966	0.07	-	0.3
36967	0.04	-	0.3
36968	0.12	-	0.7
36969	0.32	-	1.2
36970	0.05	-	0.7
36971	0.05	0.07	0.3
36972	0.07	-	0.1
36973	0.01	-	0.2
36974	0.03	-	0.2
36975	2.82	-	0.1
36976	0.02	-	0.4
36977	0.01	-	0.5
36978	0.18	-	0.3
36979	0.17	-	0.1

Certified by *Dennis Charty*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

7W-2867-RA1

Company: **OPAWICA EXPLORATIONS**

Project:

Attn: F. Sharpley

Date: SEP-10-07

Welsh

We hereby certify the following Assay of 51 Core samples submitted AUG-26-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
36980	0.24	-	0.3
36981	0.22	-	0.2
36982	0.04	-	0.2
36983	0.05	-	0.2
36984	0.07	-	0.2
36985	0.01	-	0.1
36986	0.18	-	0.3
36987	0.07	0.05	0.2
36988	0.01	-	0.2
36989	0.01	-	0.3
36990	0.01	-	0.2
36991	0.09	-	0.3
36992	0.05	-	0.1
36993	0.02	-	0.1
36994	0.04	-	0.1
36995	0.56	-	0.8
36996	0.05	-	0.1
36997	0.11	-	0.2
36998	0.18	-	0.2
36999	0.14	0.14	0.1
37000	0.48	-	0.2
Blank	0.01	-	-
STD OxK48	3.54	-	-

Certified by *Denis Chant*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

7W-2884-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Date: SEP-13-07

Project:

Attn: F. Sharpley

Welsh

We hereby certify the following Assay of 56 Core samples submitted AUG-01-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
34191	0.04	-	0.7
34192	4.06	-	1.1
34193	0.03	0.01	0.5
34194	0.01	-	1.0
34195	0.01	-	0.9
34196	0.03	-	0.7
34197	0.001	-	0.1
34198	0.06	-	0.1
34199	0.03	-	0.1
34200	0.01	-	0.1
34201	0.03	-	0.1
34202	0.01	-	0.1
34203	0.02	-	0.1
34204	0.01	-	2.1
34205	0.01	-	0.1
34206	0.04	-	0.1
34207	0.01	-	0.1
34208	0.03	-	0.4
34209	0.01	-	0.4
34210	0.02	-	0.1
34211	0.01	0.01	0.5
34212	0.63	-	1.6
34213	0.01	-	0.3
34214	0.04	-	0.7
34215	0.01	-	0.4
34216	0.01	-	0.2
34217	0.01	-	0.3
34218	0.01	-	0.3
34219	0.01	-	0.1
34220	0.01	-	0.1

Certified by *Dennis Chab...*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

7W-2884-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Project:

Attn: **F. Sharpley**

Date: SEP-13-07

Welsh

We hereby certify the following Assay of 56 Core samples submitted AUG-01-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
34221	0.01	-	0.1
34222	0.01	-	0.1
34223	0.01	-	0.1
34224	0.01	0.02	0.1
34225	0.01	-	0.1
34226	0.01	-	0.2
34227	0.01	-	0.2
34228	0.01	-	0.6
34229	0.01	-	0.9
34230	0.04	-	0.1
34231	0.01	-	0.2
34232	2.75	-	0.1
34233	0.14	0.11	0.1
34234	0.05	-	0.1
34235	0.09	-	0.1
34236	0.01	-	0.1
34237	0.03	-	0.1
34238	0.01	-	0.4
34239	0.01	-	0.9
34240	0.03	-	0.1
34241	0.14	-	0.2
34242	0.01	-	0.1
34243	0.01	-	0.5
34244	0.04	0.02	0.1
34245	0.01	-	0.1
34246	0.01	-	0.6
Blank	0.01	-	-
STD OxK47	3.58	-	-

Certified by *Dennis Christy*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

7W-2885-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Date: SEP-13-07

Project:

Attn: F. Sharpley

Welsh

We hereby certify the following Assay of 56 Core samples submitted AUG-01-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
34247	0.04	-	0.2
34248	0.02	-	0.1
34249	0.01	-	0.1
34250	0.01	-	0.1
34251	0.01	-	0.1
34252	0.59	-	0.8
34253	0.02	-	0.1
34254	0.01	-	0.1
34255	0.14	-	0.1
34256	0.18	0.08	0.1
34257	0.01	-	0.1
34258	0.07	-	0.1
34259	0.45	0.46	0.8
34260	0.04	-	0.7
34261	0.01	-	0.6
34262	0.01	-	0.1
34263	0.01	-	0.1
34264	0.01	-	0.1
34265	0.01	-	0.1
34266	0.01	-	0.1
34267	0.01	-	0.1
34268	0.03	-	1.1
34269	0.03	-	2.0
34270	0.01	-	1.3
34271	0.01	-	1.2
34272	1.82	-	33.0
34273	0.02	-	1.1
34274	0.01	-	0.2
34275	0.01	-	0.3
34276	0.01	-	0.6

Certified by *Dennis Chantre*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

7W-2885-RA1

Company: **OPAWICA RESOURCES INC.**

Date: SEP-13-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 56 Core samples submitted AUG-01-07 by .

Welsh

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
34277	0.01	-	0.1
34278	0.01	-	0.1
34279	0.01	-	0.1
34280	0.01	-	1.6
34281	0.01	-	1.7
34282	0.01	-	0.1
34283	0.01	-	1.2
34284	0.01	-	3.9
34285	0.01	-	0.2
34286	0.01	-	0.1
34287	0.01	-	0.2
34288	0.01	-	0.2
34289	0.01	-	0.1
34290	0.03	-	0.2
34291	0.01	-	0.1
34292	4.09	-	1.1
34293	0.01	-	0.1
34294	0.01	-	0.1
34295	0.03	-	0.1
34296	0.03	0.05	0.1
34297	0.01	-	0.1
34298	0.03	-	0.1
34299	0.01	-	0.1
34300	0.01	-	0.1
34301	0.03	-	0.1
34302	0.01	-	0.1
Blank	0.01	-	-
STD OXK48	3.54	-	-

Certified by *D. M. Charters*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

7W-2886-RA1

Company: **OPAWICA RESOURCES INC.**

Date: SEP-13-07

Project:
Attn: F. Sharpley

Welsh

We hereby certify the following Assay of 56 Core samples submitted AUG-01-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
34303	0.02	-	0.1
34304	0.02	-	0.1
34305	0.01	-	0.1
34306	0.02	-	0.2
34307	0.01	-	0.1
34308	0.01	-	0.1
34309	0.01	-	0.2
34310	0.03	0.03	0.2
34311	0.01	-	0.1
34312	0.61	-	1.6
34313	0.02	-	0.1
34314	0.01	-	0.3
34315	0.01	-	0.3
34316	0.01	-	0.2
34317	0.01	-	0.1
34318	0.01	-	0.2
34319	0.02	-	0.1
34320	0.01	-	0.1
34321	0.02	0.01	0.1
34322	0.01	-	0.1
34323	0.01	-	0.1
34324	0.01	-	0.1
34325	0.01	-	0.1
34326	0.01	0.01	0.1
34327	0.01	-	0.1
34328	0.01	-	0.1
34329	0.01	0.01	0.1
34330	0.01	-	0.1
34331	0.01	-	0.1
34332	2.83	-	0.1

Certified by *Denis Chroty*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

7W-2886-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Project:

Attn: F. Sharpley

Date: SEP-13-07

Welsh

We hereby certify the following Assay of 56 Core samples submitted AUG-01-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
34333	0.01	-	0.1
34334	0.01	-	0.1
34335	0.01	-	0.1
34336	0.01	-	0.1
34337	0.01	-	0.1
34338	0.01	-	0.1
34339	0.01	-	0.1
34340	0.07	0.07	0.1
34341	0.02	-	0.1
34342	0.01	-	0.1
34343	0.01	-	0.1
34344	0.01	-	0.1
34345	0.01	-	0.3
34346	0.01	-	0.2
34347	0.02	-	0.4
34348	0.01	-	0.1
34349	0.01	-	0.2
34350	0.01	-	0.2
34351	0.05	-	0.3
34352	0.59	-	1.0
34353	0.08	-	0.3
34354	0.01	-	0.1
34355	0.01	-	0.6
34356	0.09	-	1.6
34357	0.23	-	0.8
34358	0.60	0.77	0.6

Certified by *Dennis Chantre*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

7W-2887-RA1

Assay Certificate

Company: **OPAWICA REOSURCES INC.**

Date: SEP-12-07

Project:

Attn: F. Sharpley

Welsh

We hereby certify the following Assay of 56 Core samples submitted AUG-01-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
34359	0.21	-	0.4
34360	0.04	-	0.1
34361	0.04	-	0.1
34362	0.01	-	0.1
34363	0.01	-	0.2
34364	0.03	-	0.1
34365	0.01	-	0.3
34366	0.02	-	0.2
34367	0.01	0.01	0.2
34368	0.01	-	0.3
34369	0.01	-	0.3
34370	0.06	-	0.1
34401	0.07	-	0.1
34402	0.01	-	0.1
34403	0.01	-	0.2
34404	0.01	-	0.1
34405	0.01	-	0.1
34406	0.01	-	0.1
34407	0.02	-	0.1
34408	0.01	-	0.1
34409	0.01	-	0.1
34410	0.01	-	0.2
34411	0.02	-	0.1
34412	0.63	-	1.7
34413	0.01	-	0.1
34414	0.01	-	0.2
34415	0.01	-	0.1
34416	0.02	-	0.1
34417	0.01	-	0.2
34418	0.01	-	0.2

Certified by *Dennis Christie*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

7W-2887-RA1

Company: **OPAWICA REOSURCES INC.**

Date: SEP-12-07

Project:

Attn: F. Sharpley

Welsh

We hereby certify the following Assay of 56 Core samples submitted AUG-01-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
34419	0.01	-	0.1
34420	0.01	-	0.1
34421	0.01	-	0.1
34422	0.01	-	0.1
34423	0.01	0.01	0.1
34424	0.01	-	0.1
34425	0.01	-	0.1
34426	0.01	-	0.1
34427	0.01	-	0.1
34428	0.01	-	0.1
34429	0.01	-	0.1
34430	0.01	-	0.1
34431	0.01	-	0.2
34432	2.76	-	0.1
34433	0.03	-	0.1
34434	0.01	-	0.1
34435	0.01	-	0.1
34436	0.01	-	0.2
34437	0.01	-	0.1
34438	0.01	-	0.2
34439	0.01	-	0.1
34440	0.01	-	0.1
34441	0.01	-	0.1
34442	0.02	-	0.1
34443	0.01	-	0.1
34444	0.01	-	0.1
Blank	0.01	-	-
STD OXK48	3.56	-	-

Certified by *Dennis Chant*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Assay Certificate

7W-2888-RA1

Company: **OPAWICA RESOURCES INC.**

Date: SEP-10-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 26 Core samples submitted AUG-01-07 by .

Welsh

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
34445	0.01	-	0.1
34446	0.02	-	0.1
34447	0.01	-	0.1
34448	0.01	-	0.1
34449	0.01	-	0.1
34450	0.01	-	0.1
34451	0.01	-	0.1
34452	0.01	0.02	0.1
34453	0.60	-	0.8
34454	0.01	-	0.1
34455	0.01	-	0.1
34456	0.01	-	0.1
34457	0.01	-	0.1
34458	0.01	-	0.5
34459	0.01	0.01	0.3
34460	0.01	-	0.2
34461	0.01	-	0.2
34462	0.01	-	0.2
34463	0.01	-	0.1
34464	0.01	-	0.1
34465	0.01	-	0.2
34466	0.01	-	0.5
34467	0.01	-	0.1
34468	0.01	-	0.1
34469	0.01	-	0.1
34470	0.07	-	0.2
Blank	0.01	-	-
STD. OxK48	3.59	-	-

Certified by *Dennis Chalk*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

7W-2889-RA1

Company: **OPAWICA RESOURCES INC.**
Project:
Attn: F. Sharpley

Welsh

Date: SEP-14-07

We hereby certify the following Assay of 55 Core samples submitted AUG-01-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM
34561 not rec'd	-	-	-	-
34562	0.01	-	0.1	9
34563	0.01	-	0.1	7
34564	0.01	-	0.1	7
34565	0.01	0.01	0.1	49
34566	0.04	-	0.1	124
34567	0.01	-	0.1	71
34568	0.01	-	0.1	113
34569	0.01	-	0.2	52
34570	0.01	-	0.3	43
34571	0.01	-	0.1	9
34572	1.83	-	33.9	6
34573	0.01	-	0.1	116
34574	0.01	-	0.2	385
34575	0.01	-	0.1	7
34576	0.53	0.50	0.1	4
34577	0.01	-	0.1	3
34578	0.01	-	0.1	23
34579	0.01	-	0.1	94
34580	0.01	-	0.1	85
34581	0.01	-	0.1	89
34582	0.01	-	0.1	9
34583	0.01	0.01	0.1	26
34584	0.01	-	0.3	27
34585	0.01	-	0.1	41
34586	0.01	-	0.1	32
34587	0.01	-	0.1	173
34588	0.01	-	0.1	56
34589	0.01	-	0.1	80
34590	0.01	-	0.1	62

Certified by *Dennis Chroty*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

7W-2889-RA1

Company: **OPAWICA RESOURCES INC.**
Project:
Attn: F. Sharpley

Welsh

Date: SEP-14-07

We hereby certify the following Assay of 55 Core samples submitted AUG-01-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM
34591	4.07	-	0.9	6
34592	0.01	-	0.1	14
34593	0.02	-	0.1	41
34594	0.05	-	0.2	115
34595	0.35	0.40	0.1	58
34596	0.10	-	0.2	78
34597	0.02	-	0.1	135
34598	0.02	-	0.1	52
34599	0.01	-	0.1	57
34600	0.02	-	0.1	56
34601	0.01	-	0.1	10
34602	0.02	-	0.1	73
34603	0.02	-	0.1	57
34604	0.02	-	0.1	51
34605	0.03	-	0.1	64
34606	0.02	-	0.1	41
34607	0.01	-	0.1	39
34608	0.07	-	0.1	55
34609	0.01	-	0.1	33
34610	0.02	-	0.1	21
34611	0.65	-	1.7	5440
34612	0.01	-	0.1	37
34613	0.02	-	0.1	31
34614	0.01	-	0.1	33
34615	0.23	-	0.1	44
34616	0.02	-	0.1	36

Certified by *Dennis Chantre*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

7W-2890-RA1

Company: **OPAWICA RESOURCES INC.**

Date: SEP-14-07

Project:

Attn: F. Sharpley

Welsh

We hereby certify the following Assay of 34 Core samples submitted AUG-01-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM
34617	0.05	-	0.1	21
34618	0.01	-	0.1	26
34619	0.01	-	0.1	25
34620	0.01	-	0.1	9
34621	0.07	-	0.1	45
34622	0.03	-	0.1	45
34623	0.01	-	0.1	23
34624	0.03	-	0.1	16
34625	0.04	-	0.2	551
34626	0.03	-	0.1	163
34627	0.03	-	0.1	46
34628	0.08	-	0.1	18
34629	0.02	-	0.1	15
34630	2.81	-	0.1	111
34631	0.02	-	0.1	19
34632	0.16	-	0.1	16
34633	0.01	-	0.1	17
34634	0.35	-	0.1	55
34635	0.33	-	0.1	57
34636	0.13	-	0.1	46
34637	0.47	-	0.1	55
34638	0.26	-	0.1	33
34639	0.27	0.26	0.1	37
34640	0.01	-	0.1	10
34641	1.28	-	0.2	31
34642	3.41	3.17	0.6	67
34643	0.01	-	0.2	257
34644	0.01	-	0.2	82
34645	0.01	-	0.1	35
34646	0.01	-	0.2	56

Certified by *Denis Christy*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

7W-2890-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Date: SEP-14-07

Project:

Attn: F. Sharpley

Welsh

We hereby certify the following Assay of 34 Core samples submitted AUG-01-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM
34647	0.03	-	0.1	59
34648	0.01	-	0.1	85
34649	0.05	-	0.1	91
34650	0.59	-	0.9	12
Blank	0.01	-	-	-
STD OxK48	3.54	-	-	-

Certified by *Dennis Chroty*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

Assay Certificate

7W-3105-RA1

Company: **OPAWICA RESOURCES INC.**

Date: OCT-09-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 73 Core samples submitted SEP-27-07 by .

Sampling

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM
37181	0.29	0.28	0.8	-
37182	0.07	-	0.2	-
37183	0.12	-	0.3	-
37184	0.12	-	0.1	-
37185	0.07	-	0.2	-
37186	0.07	-	0.2	-
37187	0.03	-	0.3	-
37188	0.06	-	0.3	-
37189	0.64	-	1.7	-
37190	0.01	0.01	0.3	-
37191	0.01	-	0.1	-
37192	0.07	-	0.4	-
37193	0.01	-	0.5	-
37194	0.09	-	0.5	-
37195	0.10	-	0.1	-
37196	0.01	-	0.6	-
37197	0.03	-	0.6	-
37198	0.03	-	0.7	-
37199	0.01	-	0.1	-
37200	0.01	-	0.1	-
37201	0.11	0.10	0.6	-
37202	0.11	-	0.8	-
37203	0.04	-	0.7	-
37204	0.05	-	1.4	-
37205	0.02	-	0.3	-
37206	0.02	-	0.6	-
37207	0.02	-	0.4	-
37208	0.01	-	0.5	-
37209	2.85	-	0.1	-
37210	0.09	-	0.2	-

Certified by *Dennis Charters*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

7W-3105-RA1

Assay Certificate

Date: OCT-09-07

Company: **OPAWICA RESOURCES INC.**

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 73 Core samples submitted SEP-27-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM
37211	0.04	-	0.2	-
37212	0.01	-	0.1	-
37213	0.01	-	0.2	-
37214	0.01	-	0.1	-
37215	0.01	-	0.1	-
37216	0.10	0.10	0.1	-
37217	0.83	-	3.6	-
37218	0.88	-	3.6	-
37219	0.01	-	0.1	-
37220	0.01	-	0.1	-
37221	0.02	-	0.1	-
37222	0.04	-	0.1	-
37223	0.03	-	0.1	-
37224	0.03	-	0.1	-
37225	0.01	-	0.1	-
37226	0.01	-	0.2	-
37227	0.01	-	0.2	-
37228	0.01	-	0.1	-
37229	0.60	-	0.9	-
37230	0.04	-	0.1	-
44991	0.01	-	0.5	146
44992	0.01	-	0.5	119
44993	0.03	0.05	1.0	141
44994	0.01	-	0.7	132
44995	4.05	-	1.1	144
44996	0.05	-	1.0	6
44997	0.04	-	0.7	180
44998	0.04	-	0.7	234
44999	0.01	-	0.5	106
45000	0.05	-	0.8	465

Canking

Walker

Certified by *Dennis Chrosty*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

7W-3105-RA1

Date: OCT-09-07

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 73 Core samples submitted SEP-27-07 by .

walker

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM
45001	0.04	-	0.5	108
45002	0.06	0.06	0.6	207
45003	0.04	-	0.3	85
45004	0.05	-	0.5	166
45005	0.04	-	0.6	177
45006	0.01	-	0.1	9
45007	0.01	-	0.1	149
45008	0.01	-	0.1	138
45009	0.01	-	0.3	107
45010	0.01	-	1.1	100
45011	0.01	-	0.8	143
45012	0.01	-	0.5	158
45013	0.01	-	0.4	227
Blank	0.01	-	-	-
STD OxK48	3.53	-	-	-

Certified by *Penis Christ*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

7W-3106-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Date: OCT-11-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 58 Core samples submitted SEP-10-07 by .

Welsh

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
37001	0.10	-	0.1
37002	0.05	-	0.1
37003	0.05	-	0.1
37004	0.05	-	0.1
37005	0.01	-	0.1
37006	0.01	0.01	0.1
37007	0.09	-	0.2
37008	0.08	-	0.1
37009	0.01	-	0.1
37010	0.01	-	0.1
37011	0.01	-	0.1
37012	0.02	-	0.1
37013	0.01	-	0.2
37014	0.01	-	0.2
37015	1.79	-	33.6
37016	0.01	0.01	0.2
37017	0.01	-	0.3
37018	0.07	-	0.2
37019	0.06	-	0.4
37020	0.08	-	0.3
37021	0.09	-	0.4
37022	0.19	-	0.3
37023	0.01	-	0.1
37024	0.01	-	0.2
37025	0.01	-	0.1
37026	0.01	0.01	0.2
37027	0.01	-	0.2
37028	0.08	-	0.1
37029	0.07	-	0.7
37030	0.03	-	0.3

Certified by *Dennis Chanty*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

7W-3106-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Date: OCT-11-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 58 Core samples submitted SEP-10-07 by .

Welsh

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
37031	0.10	-	0.1
37032	0.01	-	0.1
37033	0.04	-	0.2
37034	0.01	-	0.1
37035	4.05	-	1.0
37036	0.04	-	0.2
37037	0.08	-	0.1
37038	0.33	-	0.2
37039	0.23	-	0.2
37040	0.30	-	0.2
37041	0.71	-	0.2
37042	0.26	-	0.1
37043	0.27	-	0.1
37044	0.31	-	0.1
37045	0.01	-	0.1
37046	0.93	0.91	0.2
37047	0.35	-	0.1
37048	0.22	-	0.1
37049	0.22	-	0.1
37050	1.10	-	0.3
37051	2.13	-	0.2
37052	0.01	-	0.2
37053	0.01	-	0.1
37054	0.01	-	0.1
37055	0.65	-	1.7
37056	0.01	-	0.1
37057	0.01	-	0.1
37058	0.06	-	0.1

Certified by *Denis Chantre*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

7W-3107-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Date: OCT-04-07

Project:

Attn: F. Sharpley

Welsh

We hereby certify the following Assay of 59 Core samples submitted SEP-10-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
37059	0.04	-	0.1
37060	0.02	-	0.1
37061	0.01	-	0.3
37062	0.01	-	0.1
37063	0.01	-	0.1
37064	0.01	-	0.3
37065	0.01	-	0.3
37066	0.01	-	0.1
37067	0.01	0.01	0.3
37068	0.01	-	0.4
37069	0.01	-	0.1
37070	0.01	-	0.2
37071	0.01	-	0.1
37072	0.01	-	0.1
37073	0.02	-	0.2
37074	0.01	-	0.5
37075	0.01	-	0.3
37076	2.72	-	0.2
37077	0.03	-	0.2
37078	0.04	-	0.1
37079	0.12	-	0.7
37080	0.03	-	0.5
37081	0.01	-	0.4
37082	0.01	-	0.4
37083	0.01	0.01	0.3
37084	0.02	-	0.3
37085	0.01	-	0.3
37086	0.01	-	0.1
37087	0.01	-	0.3
37088	0.01	-	0.2

Certified by *Demi Chant*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

7W-3107-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Date: OCT-04-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 59 Core samples submitted SEP-10-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
37089	0.01	-	0.2
37090	0.01	-	0.1
37091	0.01	-	0.2
37092	0.01	-	0.2
37093	0.01	-	0.1
37094	0.03	-	0.5
37095	0.11	-	0.4
37096	0.20	0.20	1.0
37097	0.01	-	0.1
37098	0.16	-	1.5
37099	0.04	-	0.6
37100	0.05	-	0.8
37101	0.12	-	2.3
37102	0.01	-	0.3
37103	2.79	-	0.1
37104	0.01	-	0.2
37105	0.01	-	0.1
37106	0.01	-	0.1
37107	0.01	-	0.1
37108	0.01	-	0.1
37109	0.07	0.03	0.3
37110	0.04	-	0.3
37111	0.01	-	0.2
37112	0.01	-	0.1
37113	0.01	-	0.1
37114	0.02	-	0.2
37115	0.01	-	0.1
37116	0.01	-	0.2
37117	0.01	-	0.3

welsh
↑
↓
walker
↓

Certified by *P. ...*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Assay Certificate

7W-3108-RA1

Company: **OPAWICA RESOURCES INC.**

Date: OCT-10-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 8 Core samples submitted SEP-10-07 by .

walker

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM
37118	0.11	-	1.9	2640
37119	0.10	-	1.9	2700
37120	0.45	0.34	5.3	5340
37121	0.15	-	4.4	4690
37122	0.23	-	1.6	1410
37123	0.59	-	1.0	12
37124	0.12	-	0.6	606
37125	0.04	-	0.7	272

Certified by *Denis Chantre*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

7W-3109-RA1

Date: OCT-11-07

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 55 Core samples submitted SEP-10-07 by .

walker.

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
37126	0.10	0.10	1.1
37127	0.04	-	0.5
37128	0.04	-	0.4
37129	0.01	-	0.2
37130	0.01	-	0.3
37131	0.01	-	0.2
37132	0.01	-	0.2
37133	0.01	-	0.1
37134	0.02	-	0.2
37135	0.01	-	0.3
37136	0.02	-	0.4
37137	0.01	-	0.7
37138	0.04	-	0.7
37139	0.06	-	1.6
37140	0.09	-	1.9
37141	0.02	-	0.9
37142	0.05	-	0.7
37143	1.83	-	33.7
37144	0.08	-	0.3
37145	0.01	-	0.4
37146	0.01	-	0.7
37147	0.01	-	0.7
37148	0.03	-	1.5
37149	0.02	-	0.6
37150	0.01	-	0.7
37151	0.02	-	0.8
37152	0.01	-	0.8
37153	0.01	-	0.1
37154	0.02	0.02	0.4
37155	0.01	-	0.4

Certified by *Dennis Christy*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

7W-3109-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Date: OCT-11-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 55 Core samples submitted SEP-10-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
37156	0.01	-	0.2
37157	0.01	-	0.2
37158	0.01	-	0.2
37159	0.01	-	0.1
37160	0.01	-	0.1
37161	0.01	0.01	0.2
37162	0.01	-	0.2
37163	4.05	-	1.1
37164	0.01	-	0.2
37165	0.02	-	0.3
37166	0.08	-	0.7
37167	0.01	-	0.2
37168	0.01	-	0.3
37169	0.01	-	0.1
37170	0.01	-	0.2
37171	0.01	-	0.2
37172	0.01	-	0.2
37173	0.01	-	0.1
37174	0.01	0.01	0.2
37175	0.01	-	0.1
37176	0.01	-	0.2
37177	0.01	-	0.3
37178	0.01	-	0.3
37179	0.01	-	0.3
37180	0.14	0.14	0.7 ← <i>Sampling</i>
Blank	0.01	-	-
STD OXK48	3.59	-	-

Certified by *Dennis Chantre*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Assay Certificate

7W-3110-RA1

Company: **OPAWICA RESOURCES INC.**

Date: OCT-11-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 23 Core samples submitted SEP-10-07 by .

walker

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM
44261	0.01	0.02	0.3	-
44262	0.01	-	0.2	-
44263	0.05	-	0.3	-
44264	0.11	-	0.3	-
44265	0.01	-	0.2	-
44266	0.08	-	0.5	-
44267	0.01	-	0.2	-
44268	0.02	-	0.2	-
44269	0.02	-	0.2	-
44270	0.01	-	0.1	-
44271	0.04	-	0.2	-
44272	0.01	-	0.2	-
44273	0.03	-	0.1	-
44274	0.01	-	0.3	-
44275	0.03	0.03	0.2	118
44276	0.07	-	0.2	121
44277	0.03	-	0.2	374
44278	0.06	0.06	0.3	422
44279	0.03	-	0.1	148
44280	1.83	-	33.2	7
44281	0.05	-	0.3	502
44282	0.01	-	0.3	633
44283	0.13	-	0.3	637
Blank	0.01	-	-	-
STD OxK48	3.63	-	-	-

Certified by *Dennis Chant*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

7W-3111-RA1

Company: **OPAWICA RESOURCES INC.**

Date: OCT-10-07

Project:

Attn: F. Sharpley

Walker

We hereby certify the following Assay of 59 Core samples submitted SEP-10-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM	Mo PPM
44284	0.01	-	0.7	927	14
44285	0.38	-	0.4	471	15
44286	0.01	-	0.6	1270	8
44287	0.01	-	0.2	548	3
44288	0.04	0.01	0.5	1700	10
44289	0.01	-	0.7	1730	11
44290	0.01	-	0.1	9	1
44291	0.01	-	0.6	1270	11
44292	0.71	0.67	1.9	411	10
44293	0.04	-	0.4	772	3
44294	0.09	-	0.7	1170	17
44295	0.05	-	0.6	497	7
44296	0.38	-	1.8	33	23
44297	0.07	-	0.8	576	12
44298	0.04	-	0.6	134	3
44299	0.01	-	0.2	51	3
44300	4.05	-	1.2	7	1
44301	0.01	-	0.2	203	7
44302	0.01	-	0.3	183	15
44303	0.02	-	0.2	200	8
44304	0.01	0.01	0.4	253	2
44305	0.01	-	0.2	185	5
44306	0.01	-	0.4	197	4
44307	0.01	-	0.7	540	9
44308	0.01	-	0.4	472	4
44309	3.75	-	22.8	73	56
44310	3.57	-	22.6	61	53
44311	0.01	-	0.1	9	1
44312	0.01	-	1.0	1440	5
44313	0.01	-	1.3	1320	28

Certified by

Denis Chanty



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

7W-3111-RA1

Company: **OPAWICA RESOURCES INC.**

Date: OCT-10-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 59 Core samples submitted SEP-10-07 by .

Walker

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM	Mo PPM
44314	0.01	-	0.2	149	4
44315	0.01	-	0.2	61	6
44316	0.03	-	0.1	171	6
44317	0.09	-	1.0	953	273
44318	0.08	-	0.8	966	32
44319	0.02	-	0.2	407	8
44320	0.01	-	0.1	207	5
44321	0.60	-	1.7	5450	3
44322	0.01	-	0.2	600	81
44323	0.06	-	0.2	1020	73
44324	0.03	0.01	0.2	522	6
44325	0.06	-	0.2	1010	13
44326	0.01	-	0.3	493	8
44327	0.01	-	0.1	308	7
44328	0.04	-	0.1	253	3
44329	0.03	-	0.1	509	9
44330	0.01	-	0.1	507	9
44331	0.01	-	0.1	9	1
44332	0.03	-	0.1	446	7
44333	0.01	-	0.2	703	12
44334	0.06	-	0.3	752	44
44335	0.01	-	0.2	543	17
44336	0.03	-	0.2	578	5
44337	0.01	-	0.1	654	4
44338	0.01	-	0.1	520	14
44339	0.01	0.01	0.6	1180	16
44340	0.01	-	0.1	545	5
44341	2.74	-	0.1	110	2
44342	0.06	-	0.4	1030	8

Certified by

Don Chanty



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

7W-3112-RA1

Company: **OPAWICA RESOURCES INC.**

Project:

Attn: F. Sharpley

Walker

Date: OCT-08-07

We hereby certify the following Assay of 58 Core samples submitted SEP-10-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM	Mo PPM
44343	0.06	-	0.7	1010	16
44344	0.07	-	0.9	888	26
44345	0.01	-	0.7	612	25
44346	0.07	-	0.9	1150	25
44347	0.04	-	0.6	704	32
44348	0.09	0.07	1.2	1620	48
44349	0.08	-	1.5	2510	65
44350	0.01	-	1.5	2400	68
44351	0.01	-	0.1	8	1
44352	0.07	-	0.7	766	33
44353	0.09	-	0.9	1090	24
44354	0.01	-	0.7	661	17
44355	0.41	-	1.1	1050	39
44356	0.12	-	0.8	749	34
44357	0.13	-	0.6	577	27
44358	0.11	-	0.8	872	22
44359	0.04	-	0.5	706	14
44360	0.07	-	0.8	1010	11
44361	0.60	-	0.9	13	1
44362	0.01	0.01	0.5	1320	28
44363	0.01	-	0.6	729	37
44364	0.03	-	0.9	857	20
44365	0.01	-	0.4	245	5
44366	0.06	-	0.4	730	21
44367	0.11	-	0.5	1120	22
44368	0.01	-	0.8	921	22
44369	0.01	-	0.7	957	30
44370	0.04	-	0.6	948	28
44371	0.01	-	0.1	9	1
44372	0.10	0.13	0.7	1450	34

Certified by *Dominic Chant*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

7W-3112-RA1

Company: OPAWICA RESOURCES INC.

Date: OCT-08-07

Project:

Attn: F. Sharpley

Walker

We hereby certify the following Assay of 58 Core samples submitted SEP-10-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM	Mo PPM
44373	0.10	-	0.6	1280	20
44374	0.01	-	0.3	488	15
44375	0.07	-	0.4	769	15
44376	0.05	-	0.5	1120	25
44377	0.01	-	0.3	1020	20
44378	0.05	-	0.6	1010	52
44379	0.09	-	0.6	1280	21
44380	0.08	-	0.7	1430	55
44381	1.80	-	33.6	9	1
44382	0.05	-	0.3	283	10
44383	0.07	-	0.4	1020	38
44384	0.06	-	0.4	829	8
44385	0.04	-	0.2	289	15
44386	0.01	-	0.2	507	6
44387	0.05	-	0.2	373	15
44388	0.04	-	0.2	242	5
44389	0.03	-	0.1	117	7
44390	0.03	-	0.1	112	7
44391	0.01	-	0.1	9	1
44392	0.01	-	0.4	498	14
44393	0.01	0.01	0.1	201	8
44394	0.01	-	0.2	523	10
44395	0.21	-	1.0	832	19
44396	0.02	-	0.7	1570	5
44397	0.08	-	0.1	841	4
44398	0.01	-	0.2	737	8
44399	0.01	-	0.6	1530	28
44400	0.11	-	0.4	934	5

Certified by *Dennis Chisholm*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

7W-3113-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Date: OCT-09-07

Project:

Attn: F. Sharpley

Walker

We hereby certify the following Assay of 80 Core samples submitted SEP-26-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM
44911	0.01	-	0.2	98
44912	0.01	-	0.2	84
44913	0.01	-	0.3	108
44914	0.01	-	0.1	74
44915	0.64	-	1.8	5460
44916	0.01	-	0.2	137
44917	0.01	-	0.7	60
44918	0.01	-	0.5	69
44919	0.01	-	0.4	105
44920	0.01	-	0.2	121
44921	0.01	-	0.2	116
44922	0.01	0.01	0.1	94
44923	0.01	-	0.3	92
44924	0.01	-	0.3	81
44925	0.01	-	0.3	77
44926	0.01	-	0.1	10
44927	0.01	-	0.3	205
44928	0.01	-	0.2	95
44929	0.01	-	0.5	91
44930	0.01	-	0.1	45
44931	0.01	-	0.1	120
44932	0.01	-	0.5	148
44933	0.01	-	0.3	171
44934	0.01	-	0.2	43
44935	0.01	-	0.3	84
44936	2.92	-	0.1	104
44937	0.01	-	0.2	29
44938	0.01	0.01	0.1	26
44939	0.03	-	0.3	95
44940	0.01	-	0.1	141

Certified by

Demi Chasty



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

Assay Certificate

7W-3113-RA1

Company: **OPAWICA RESOURCES INC.**

Date: OCT-09-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 80 Core samples submitted SEP-26-07 by .

Walker

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM
44941	0.02	-	0.5	240
44942	0.01	-	0.3	251
44943	0.01	-	0.2	155
44944	0.01	-	0.3	146
44945	0.01	-	0.5	155
44946	0.01	-	0.1	10
44947	0.03	-	0.7	183
44948	0.02	-	0.2	223
44949	0.03	-	0.4	157
44950	0.01	0.01	0.5	147
44951	0.01	-	0.7	180
44952	0.01	-	0.3	204
44953	0.02	-	0.5	188
44954	0.01	-	0.6	214
44955	0.01	-	0.4	159
44956	0.59	-	0.7	9
44957	0.01	-	0.5	198
44958	0.01	-	0.5	306
44959	0.01	-	0.6	165
44960	0.01	-	0.4	436
44961	0.03	-	0.7	472
44962	0.01	-	0.2	171
44963	0.01	-	0.2	215
44964	0.03	0.03	0.5	272
44965	0.01	-	0.4	319
44966	0.01	-	0.1	10
44967	0.01	-	0.2	187
44968	0.01	-	0.3	141
44969	0.02	-	0.2	61
44970	0.01	-	0.1	212

Certified by *Denis Chroby*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

7W-3113-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Date: OCT-09-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 80 Core samples submitted SEP-26-07 by .

Walker

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM
44971	0.01	-	0.3	65
44972	0.01	-	0.5	94
44973	0.02	-	0.8	118
44974	0.03	-	1.1	266
44975	0.01	-	0.7	146
44976	1.75	-	33.7	7
44977	0.01	-	0.9	186
44978	0.02	-	0.8	129
44979	0.03	-	0.8	127
44980	0.01	-	0.9	92
44981	0.01	-	1.2	67
44982	0.01	-	1.6	77
44983	0.06	-	2.3	185
44984	0.01	-	1.8	100
44985	0.03	-	1.5	118
44986	0.01	-	0.1	9
44987	0.03	-	1.0	84
44988	0.03	-	1.5	117
44989	0.03	-	1.1	162
44990	0.04	-	1.1	193
Blank	0.01	-	-	-
STD OxK48	3.56	-	-	-

Certified by

Devin Chant

1 Cameron Ave., P.O. Box 10, Swastika, Ontario P0K 1T0

Telephone (705) 642-3244

Fax (705) 642-3300



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Assay Certificate

7W-3115-RA1

Company: **OPAWICA EXPLORATIONS INC.**

Date: OCT-09-07

Project:

Attn: F. Sharpley

Walker

We hereby certify the following Assay of 20 Core samples submitted SEP-24-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM	Mo %
44401	3.98	-	0.9	8	<5
44402	0.04	-	0.7	721	8
44403	0.02	-	1.0	937	<5
44404	0.03	-	0.7	468	<5
44405	0.04	-	0.5	470	<5
44406	0.05	-	0.7	781	24
44407	0.01	-	0.8	894	14
44408	0.05	-	0.8	891	<5
44409	0.03	-	1.0	1130	<5
44410	0.05	-	0.9	1130	<5
44411	0.01	-	0.1	10	<5
44412	0.04	-	0.7	888	8
44413	0.10	0.10	2.4	415	13
44414	0.32	-	4.2	231	45
44415	0.03	-	1.4	1110	11
44416	0.07	-	1.2	485	50
44417	0.05	-	1.7	1070	6
44418	0.05	-	1.5	1040	69
44419	0.01	-	0.7	581	120
44420	0.08	-	0.8	913	7

Certified by *Denis Chant*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Assay Certificate

7W-3116-RA1

Company: **OPAWICA EXPLORATIONS INC.**

Date: OCT-11-07

Project:

Attn: F. Sharpley

Walker

We hereby certify the following Assay of 23 Core samples submitted SEP-24-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
44421	0.61	-	1.8
44422	0.01	-	0.1
44423	0.01	-	0.2
44424	0.01	-	0.4
44425	0.01	-	0.3
44426	0.01	0.01	0.2
44427	0.01	-	0.1
44428	0.02	0.02	0.1
44429	0.01	-	0.1
44430	0.01	-	0.1
44431	0.01	-	0.1
44432	0.01	-	0.1
44433	0.01	-	0.2
44434	0.01	-	0.3
44435	0.01	-	0.1
44436	0.01	-	0.3
44437	0.01	-	0.3
44438	0.01	-	0.3
44439	0.01	-	0.3
44440	0.01	-	0.7
44441	2.82	-	0.1
44442	0.35	-	1.2
44443	1.22	1.29	2.8

Certified by *Dennis Chrosty*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Assay Certificate

7W-3117-RA1

Company: **OPAWICA EXPLORATIONS INC.**

Date: OCT-09-07

Project:

Attn: F. Sharpley

Walker

We hereby certify the following Assay of 27 Core samples submitted SEP-24-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM
44444	0.01	0.01	0.2	79
44445	0.01	-	0.4	190
44446	0.01	-	0.3	166
44447	0.01	-	0.5	141
44448	0.01	-	0.2	119
44449	0.01	-	0.4	335
44450	0.01	-	0.4	275
44451	0.01	-	0.1	10
44452	0.01	0.01	0.2	243
44453	0.02	-	0.3	149
44454	0.03	-	0.4	313
44455	0.01	-	0.4	231
44456	0.01	-	0.2	385
44457	0.01	-	0.3	97
44458	0.01	-	0.1	530
44459	0.01	0.01	0.4	425
44460	0.01	-	0.5	152
44461	0.59	-	0.8	11
44462	0.01	-	0.1	145
44463	0.01	-	0.3	158
44464	0.01	-	0.2	228
44465	0.01	-	0.2	212
44466	0.01	-	0.3	413
44467	0.01	0.01	0.1	193
44468	0.01	-	0.2	180
44469	0.01	-	0.2	173
44470	0.01	-	0.2	195
Blank	0.01	-	-	-
STD OxK48	3.55	-	-	-

Certified by *Diana Chanty*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

7W-3118-RA1

Assay Certificate

Company: **OPAWICA EXPLORATIONS INC.**

Date: OCT-16-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 56 Core samples submitted SEP-26-07 by .

Walker

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
44471	0.01	-	0.1
44472	0.13	-	0.2
44473	0.01	0.01	0.5
44474	0.01	-	0.2
44475	0.01	-	0.1
44476	0.01	-	0.2
44477	0.01	-	0.3
44478	0.01	-	0.3
44479	0.01	-	0.1
44480	0.01	-	0.4
44481	1.77	-	33.7
44482	0.01	-	0.1
44483	0.01	-	0.1
44484	0.04	-	0.1
44485	0.01	-	0.4
44486	0.01	-	0.1
44487	1.12	-	0.4
44488	0.08	0.06	0.3
44489	0.01	-	0.1
44490	0.03	-	0.1
44491	0.01	-	0.1
44492	0.01	-	0.1
44493	0.01	-	0.2
44494	0.01	-	0.1
44495	0.01	-	0.1
44496	0.02	0.02	0.1
44497	0.01	-	0.1
44498	0.02	-	0.1
44499	0.07	-	0.1
44500	0.03	-	0.2

Certified by *Dennis Chate*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

7W-3118-RA1

Assay Certificate

Company: **OPAWICA EXPLORATIONS INC.**

Date: OCT-16-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 56 Core samples submitted SEP-26-07 by .

Walker

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
44501	3.98	-	1.0
44502	0.01	-	0.2
44503	0.01	-	0.3
44504	0.01	-	0.7
44505	0.01	-	0.5
44506	0.01	0.02	0.3
44507	0.01	-	0.1
44508	0.01	-	0.2
44509	0.04	-	0.1
44510	0.01	-	0.1
44511	0.05	-	0.3
44512	0.05	-	0.3
44513	0.01	-	0.2
44514	0.04	-	0.5
44515	0.01	-	0.1
44516	0.01	-	0.1
44517	0.01	-	0.1
44518	0.01	-	0.2
44519	0.63	-	1.8
44520	0.01	0.01	0.2
44521	0.01	-	0.2
44522	0.01	-	0.6
44523	0.01	-	0.2
44524	0.01	-	0.1
44525	0.01	-	0.2
44526	0.01	-	0.2
Blank	0.01	-	-
STD OxK48	3.63	-	-

Certified by

Dennis Christie



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

7W-3119-RA1

Date: OCT-11-07

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Project:

Attn: F. Sharpley

Walker

We hereby certify the following Assay of 55 Core samples submitted SEP-24-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
44527	0.01	-	0.1
44528	0.01	-	0.1
44529	0.01	-	0.1
44530	0.01	-	0.2
44531	0.01	-	0.1
44532	0.01	0.02	0.1
44533	0.03	-	0.1
44534	0.01	-	0.1
44535	0.01	-	0.1
44536	0.01	-	0.2
44537	0.02	-	0.2
44538	0.01	-	0.2
44539	2.81	-	0.1
44540	0.01	-	0.1
44541	0.01	-	0.3
44542	0.03	-	0.2
44543	0.01	-	0.1
44544	0.01	-	0.2
44545	0.02	-	0.3
44546	0.01	0.02	0.4
44547	0.01	-	0.3
44548	0.01	-	0.3
44549	0.01	-	0.1
44550	0.01	-	0.1
44551	0.01	-	0.2
44552	0.01	-	0.1
44553	0.07	-	0.3
44554	0.15	0.16	0.4
44555	0.01	-	0.1
44556	0.01	-	0.1

Certified by *Dennis Chisholm*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

7W-3119-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Date: OCT-11-07

Project:

Attn: F. Sharpley

walker

We hereby certify the following Assay of 55 Core samples submitted SEP-24-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
44557	0.01	-	0.1
44558	0.01	-	0.1
44559	0.58	-	0.9
44560	0.01	-	0.1
44561	0.02	0.01	0.1
44562	0.03	-	0.2
44563	0.01	-	0.1
44564	0.05	-	0.2
44565	0.01	-	0.1
44566	0.01	-	0.1
44567	0.01	-	0.1
44568	0.02	-	0.1
44569	0.01	-	0.1
44570	0.01	-	0.1
44571	0.01	0.01	0.3
44572	0.01	-	0.1
44573	0.02	-	0.1
44574	0.01	-	0.1
44575	0.01	-	0.1
44576	0.01	-	0.1
44577	0.01	0.01	0.1
44578	0.01	-	0.1
44579	1.80	-	33.0
44580	0.01	-	0.1
44581	0.01	-	0.1
Blank	0.01	-	-
STD OxK48	3.48	-	-

Certified by *Dennis Chant*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

7W-3120-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Project:

Attn: F. Sharpley

Date: OCT-16-07

Walker

We hereby certify the following Assay of 55 Core samples submitted SEP-24-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
44582	0.05	-	0.1
44583	0.02	-	0.1
44584	0.05	-	0.1
44585	0.01	-	0.1
44586	0.06	-	0.1
44587	0.06	0.07	0.3
44588	0.04	-	0.2
44589	0.01	-	0.1
44590	0.04	-	0.1
44591	0.04	-	0.1
44592	0.04	-	0.1
44593	0.03	-	0.2
44594	0.03	-	0.1
44595	0.06	-	0.1
44596	0.04	-	0.1
44597	0.04	-	0.1
44598	0.20	0.19	0.7
44599	4.06	-	1.0
44600	0.07	-	0.1
44601	0.03	-	0.2
44602	0.03	-	0.1
44603	0.05	-	0.1
44604	0.05	-	0.2
44605	0.04	-	0.1
44606	0.08	-	0.4
44607	0.02	-	0.1
44608	0.03	-	0.1
44609	0.01	-	0.1
44610	0.04	0.04	0.3
44611	0.01	-	0.1

Certified by *Denis Chant*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

7W-3120-RA1

Company: **OPAWICA RESOURCES INC.**

Project:

Attn: F. Sharpley

Date: OCT-16-07

Walker

We hereby certify the following Assay of 55 Core samples submitted SEP-24-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
44612	0.02	-	0.6
44613	0.02	-	0.6
44614	0.01	-	0.1
44615	0.01	0.01	0.1
44616	0.18	-	1.6
44617	0.34	-	2.3
44618	0.01	-	0.2
44619	0.03	-	0.4
44620	0.62	-	1.7
44621	0.01	-	0.2
44622	0.03	-	0.1
44623	0.06	-	0.4
44624	0.03	-	0.2
44625	0.05	0.05	0.4
44626	0.03	-	0.4
44627	0.12	-	1.0
44628	0.01	-	0.2
44629	0.01	-	0.1
44630	0.01	-	0.1
44631	0.02	-	0.3
44632	0.02	-	0.3
44633	0.01	-	0.1
44634	0.01	-	0.4
44635	0.06	-	1.3
44636	0.02	0.01	0.2
Blank	0.01	-	-
STD OxK48	3.54	-	-

Certified by *Devin Chanty*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

7W-3121-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Date: OCT-16-07

Project:

Attn: F. Sharpley

Walker

We hereby certify the following Assay of 56 Core samples submitted SEP-24-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
44637	0.01	-	0.2
44638	0.01	-	0.1
44639	2.84	-	0.1
44640	0.01	-	0.3
44641	0.01	0.01	0.2
44642	0.01	-	0.5
44643	0.02	-	0.5
44644	0.02	-	0.7
44645	0.01	-	0.3
44646	0.31	-	0.3
44647	0.01	-	0.2
44648	0.01	-	0.2
44649	0.01	-	0.1
44650	0.18	-	0.6
44651	0.23	-	0.5
44652	0.01	-	0.3
44653	0.14	0.12	0.7
44654	0.01	-	0.2
44655	0.01	-	0.3
44656	0.01	-	0.3
44657	0.01	-	0.4
44658	0.01	-	0.2
44659	0.61	-	0.9
44660	0.01	-	0.3
44661	0.03	-	0.1
44662	0.01	-	0.2
44663	0.01	0.01	0.3
44664	0.03	-	0.2
44665	0.01	-	0.1
44666	0.01	-	0.1

Certified by *Dennis Chantler*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

7W-3121-RA1

Company: **OPAWICA RESOURCES INC.**

Walker

Date: OCT-16-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 56 Core samples submitted SEP-24-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
44667	0.01	-	0.1
44668	0.01	-	0.2
44669	0.01	-	0.2
44670	1.81	-	33.9
44671	0.09	-	0.1
44672	0.01	-	0.3
44673	0.01	-	0.2
44674	0.01	-	0.1
44675	0.01	-	0.1
44676	0.01	0.02	0.8
44677	0.05	-	0.5
44678	0.12	-	0.8
44679	0.13	-	0.6
44680	0.01	-	0.1
44681	0.20	-	0.5
44682	0.11	-	1.1
44683	0.08	-	0.7
44684	0.07	-	0.5
44685	0.02	-	0.7
44686	0.01	0.01	0.8
44687	0.01	-	0.2
44688	0.02	-	0.2
44689	0.01	-	0.2
44690	4.03	-	0.9
44691	0.01	-	0.7
44692	0.01	-	0.2
Blank	0.01	-	-
STD OxK48	3.60	-	-

Certified by *D. [Signature]*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

7W-3122-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Project:

Attn: F. Sharpley

Date: OCT-16-07

Walker

We hereby certify the following Assay of 46 Core samples submitted SEP-24-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM
44693	0.02	0.03	0.3	-
44694	0.01	-	0.3	-
44695	0.01	-	0.2	-
44696	0.03	-	0.3	-
44697	0.33	-	0.2	-
44698	0.10	-	0.5	-
44699	0.10	-	0.6	-
44700	0.01	-	0.1	-
44701	0.20	-	1.1	-
44702	0.09	-	0.5	-
44703	0.06	-	0.8	-
44704	0.05	0.07	0.3	-
44705	0.01	-	0.5	-
44706	0.01	-	0.2	-
44707	0.01	-	0.2	-
44708	0.04	-	0.6	-
44709	0.61	-	1.8	-
44710	0.08	-	0.4	-
44711	0.05	-	0.9	-
44712	0.01	-	0.7	-
44713	0.04	-	0.2	-
44714	0.27	-	1.8	2600
44715	0.06	-	0.5	457
44716	0.02	-	0.3	34
44717	0.02	-	0.1	17
44718	0.02	-	0.2	18
44719	0.01	-	0.1	10
44720	0.01	-	0.2	14
44721	0.02	0.01	0.1	24
44722	0.02	-	0.1	24

Certified by *Dennis Christy*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

7W-3122-RA1

Company: **OPAWICA RESOURCES INC.**

Project:

Attn: F. Sharpley

Date: OCT-16-07

Walker

We hereby certify the following Assay of 46 Core samples submitted SEP-24-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu PPM
44723	0.01	-	0.1	34
44724	0.02	-	0.1	39
44725	0.02	-	0.1	9
44726	0.01	-	0.1	82
44727	0.02	-	0.1	15
44728	0.01	0.01	0.2	70
44729	2.82	-	0.1	110
44730	0.01	-	0.2	100
44731	0.01	-	0.1	37
44732	0.01	-	0.1	30
44733	0.01	0.01	0.1	48
44734	0.01	-	0.1	47
44735	0.01	-	0.1	43
44736	0.01	-	0.1	98
44737	0.03	-	0.1	14
44738	0.01	-	0.1	16
Blank	0.01	-	-	-
STD OxK48	3.56	-	-	-

Certified by

Dennis Chantler

1 Cameron Ave., P.O. Box 10, Swastika, Ontario P0K 1T0
Telephone (705) 642-3244 Fax (705) 642-3300



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

7W-3123-RA1

Company: **OPAWICA RESOURCES INC.**

Date: OCT-09-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 56 Core samples submitted SEP-24-07 by .

walker

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
44739	0.01	-	0.1
44740	0.01	-	0.1
44741	0.01	0.01	0.2
44742	0.01	-	0.3
44743	0.02	-	0.2
44744	0.05	-	0.2
44745	0.02	-	0.1
44746	0.01	-	0.2
44747	0.01	-	0.2
44748	0.01	-	0.1
44749	0.60	-	0.8
44750	0.01	-	0.2
44751	0.11	-	1.4
44752	0.21	-	1.9
44753	0.07	-	1.1
44754	0.07	0.01	1.2
44755	0.04	-	0.8
44756	0.23	-	1.9
44757	0.01	-	0.9
44758	0.04	-	0.8
44759	0.01	-	0.1
44760	0.05	-	0.8
44761	0.04	-	0.9
44762	0.01	-	1.1
44763	0.01	-	0.2
44764	0.01	-	0.8
44765	0.01	-	0.7
44766	0.03	-	0.4
44767	0.02	0.01	0.6
44768	0.01	-	0.5

Certified by *Dennis Chantre*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

7W-3123-RA1

Company: **OPAWICA RESOURCES INC.**

Date: OCT-09-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 56 Core samples submitted SEP-24-07 by .

walker

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
44769	0.03	-	0.8
44770	0.05	-	0.1
44771	0.21	-	0.7
44772	0.03	-	0.4
44773	0.05	-	0.6
44774	0.01	-	0.4
44775	1.79	-	33.1
44776	0.43	-	0.9
44777	0.55	0.51	1.1
44778	0.04	-	0.1
44779	0.02	-	0.2
44780	0.02	-	0.5
44781	0.03	-	0.4
44782	0.08	-	1.1
44783	0.03	-	0.5
44784	0.01	-	0.5
44785	0.01	-	0.10
44786	0.01	-	0.9
44787	0.01	-	0.3
44788	0.01	-	0.3
44789	0.04	-	0.7
44790	0.01	-	0.6
44791	0.01	-	0.7
44792	0.01	-	0.7
44793	0.01	0.01	0.5
44794	0.01	-	0.5
Blank	0.01	-	-
STD OXK48	3.51	-	-

Certified by *Dennis Chant*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

7W-3124-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Project:

Date: OCT-10-07

Attn: F. Sharpley

We hereby certify the following Assay of 56 Core samples submitted SEP-24-07 by .

Walker

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
44795	4.11	-	1.0
44796	0.01	-	0.2
44797	0.01	0.04	0.2
44798	0.01	-	0.7
44799	0.01	-	0.1
44800	0.01	-	0.1
44801	0.01	-	0.1
44802	0.01	-	0.2
44803	0.01	-	0.1
44804	0.01	-	0.1
44805	0.01	-	0.1
44806	0.01	0.01	0.1
44807	0.01	-	0.1
44808	0.01	-	0.1
44809	0.01	-	0.1
44810	0.01	-	0.1
44811	0.01	-	0.1
44812	0.01	-	0.1
44813	0.01	-	0.1
44814	0.01	-	0.1
44815	0.64	-	1.7
44816	0.01	-	0.1
44817	0.01	-	0.1
44818	0.01	-	0.1
44819	0.01	-	0.1
44820	0.01	-	0.1
44821	0.01	-	0.1
44822	0.01	0.01	0.1
44823	0.01	-	0.1
44824	0.01	-	0.1

Certified by *Dennis Chant*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

7W-3124-RA1

Company: **OPAWICA RESOURCES INC.**

Date: OCT-10-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 56 Core samples submitted SEP-24-07 by .

Walker

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
44825	0.01	-	0.1
44826	0.02	-	0.1
44827	0.03	-	0.1
44828	0.11	-	0.1
44829	0.01	-	0.1
44830	0.01	-	0.1
44831	0.01	-	0.1
44832	0.01	-	0.1
44833	0.01	-	0.1
44834	0.13	-	0.1
44835	2.85	-	0.1
44836	0.30	0.31	0.7
44837	0.07	-	0.1
44838	0.03	-	0.1
44839	0.07	-	0.2
44840	0.01	-	0.1
44841	0.01	-	0.1
44842	0.01	-	0.1
44843	0.01	-	0.1
44844	0.01	-	0.1
44845	0.01	-	0.1
44846	0.01	-	0.1
44847	0.01	-	0.1
44848	0.02	-	0.1
44849	0.01	-	0.1
44850	0.01	0.01	0.1
Blank	0.01	-	-
STD OxK48	3.57	-	-

Certified by *Dennis Chantre*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

7W-3125-RA1

Company: **OPAWICA RESOURCES INC.**

Date: OCT-11-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 60 Core samples submitted SEP-24-07 by .

Walker

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
44851	0.01	0.01	0.3
44852	0.01	-	0.2
44853	0.01	-	0.2
44854	0.01	-	0.6
44855	0.60	-	0.9
44856	0.01	-	0.2
44857	0.01	-	0.4
44858	0.01	-	0.2
44859	0.02	-	0.1
44860	0.01	-	0.1
44861	0.01	-	0.1
44862	0.01	-	0.1
44863	0.01	-	0.4
44864	0.01	-	0.4
44865	0.01	-	0.1
44866	0.01	-	0.1
44867	0.01	-	0.1
44868	0.01	0.01	0.1
44869	0.01	-	0.1
44870	0.01	-	0.1
44871	0.01	-	0.2
44872	0.01	-	0.2
44873	0.01	-	0.1
44874	0.01	-	0.2
44875	1.75	-	33.1
44876	0.04	-	1.4
44877	0.02	-	0.5
44878	0.01	-	0.4
44879	0.01	-	0.1
44880	0.01	-	0.1

Certified by *Dennis Chisholm*

1 Cameron Ave., P.O. Box 10, Swastika, Ontario P0K 1T0
Telephone (705) 642-3244 Fax (705) 642-3300



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

7W-3125-RA1

Company: OPAWICA RESOURCES INC.

Date: OCT-11-07

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 60 Core samples submitted SEP-24-07 by .

Walker.

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne
44881	0.01	-	0.5
44882	0.01	-	0.4
44883	0.01	-	0.3
44884	0.01	-	0.3
44885	0.01	-	0.1
44886	0.01	-	0.7
44887	0.01	-	0.4
44888	0.01	-	0.4
44889	0.01	-	0.3
44890	0.01	-	0.2
44891	0.04	-	1.2
44892	0.05	0.07	3.7
44893	0.07	-	4.4
44894	0.10	-	15.4
44895	4.11	-	1.0
44896	0.01	-	1.1
44897	0.06	-	4.8
44898	0.01	-	2.0
44899	0.01	-	1.1
44900	0.02	-	2.1
44901	0.01	-	1.0
44902	0.01	-	0.4
44903	0.02	-	0.3
44904	0.02	-	0.3
44905	0.01	-	0.1
44906	0.01	-	0.3
44907	0.02	-	1.0
44908	0.02	-	0.9
44909	0.01	-	0.8
44910	0.01	-	0.1

Certified by *Dennis Chantler*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

7W-3214-RA1

Company: **OPAWICA RESOURCES INC.**

Project:

Attn: F. Sharpley

Date: OCT-22-07

Cambeing

We hereby certify the following Assay of 56 Core samples submitted OCT-01-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
37231	0.01	-	0.2
37232	0.01	-	0.1
37233	0.01	-	0.2
37234	0.01	-	0.1
37235	0.03	-	0.1
37236	0.11	0.10	0.4
37237	0.08	-	0.5
37238	0.09	-	0.4
37239	0.05	-	0.3
37240	0.33	-	2.4
37241	0.31	-	2.4
37242	0.01	-	0.1
37243	0.20	-	1.1
37244	0.94	0.94	5.3
37245	0.79	-	5.4
37246	0.04	-	0.2
37247	0.01	-	0.4
37248	0.04	-	0.5
37249	0.04	-	0.7
37250	0.10	0.10	0.8
37251	0.04	-	0.7
37252	1.77	-	33.2
37253	0.10	-	2.1
37254	0.04	-	0.8
37255	0.05	-	0.9
37256	0.01	-	0.4
37257	0.06	0.05	0.3
37258	0.09	-	0.7
37259	0.14	-	1129.3
37260	0.18	-	1.3

Certified by

Denis Charle



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

7W-3214-RA1

Assay Certificate

Company: **OPAWICA RESOURCES INC.**

Project:

Attn: F. Sharpley

Date: OCT-22-07

Sampling

We hereby certify the following Assay of 56 Core samples submitted OCT-01-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
37261	0.16	-	0.7
37262	0.01	-	0.1
37263	0.04	-	0.5
37264	0.11	-	0.6
37265	0.11	-	0.6
37266	0.09	-	0.7
37267	0.08	0.09	0.4
37268	0.05	-	0.6
37269	0.07	-	0.6
37270	0.09	-	0.7
37271	0.08	-	0.6
37272	4.01	-	1.1
37273	0.05	-	0.2
37274	0.07	-	0.1
37275	0.05	-	0.1
37276	0.06	-	0.2
37277	0.04	-	0.2
37278	0.03	-	0.1
37279	0.06	-	0.2
37280	0.01	-	0.2
37281	0.01	-	0.2
37282	0.01	-	0.1
37283	0.02	0.01	0.1
37284	0.01	-	0.1
37285	0.02	-	0.1
37286	0.01	-	0.1
Blank	0.01	-	-
STD OxK48	3.51	-	-

Certified by *Dennis Charles*



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

7W-3215-RA1

Company: **OPAWICA RESOURCES INC.**

Date: OCT-19-07

Project:

Attn: F, Sharpley

BANNOCKBURN

We hereby certify the following Assay of 54 Core samples submitted OCT-01-07 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag PPM
37287	0.01	-	0.1
37288	0.03	-	0.1
37289	0.05	0.04	0.1
37290	0.01	-	0.1
37291	0.08	-	0.1
37292	0.63	-	1.7
37293	0.23	-	0.1
37294	0.12	-	0.1
37295	0.01	-	0.1
37296	0.02	-	0.1
37297	0.06	-	0.1
37298	0.01	-	0.1
37299	0.01	-	0.1
37300	0.05	0.03	0.1
37301	0.02	-	0.1
37302	0.03	-	0.1
37303	0.01	-	0.1
37304	0.03	-	0.1
37305	0.01	-	0.1
37306	0.60	-	1.7
37307	0.01	-	0.1
37308	0.02	-	0.1
37309	0.01	-	0.1
37310	0.02	0.01	0.1
37311	0.01	-	0.1
37312	0.03	-	0.1
37313	0.01	-	0.1
37314	0.02	-	0.1
37315	0.03	-	0.1
37316	0.01	-	0.1

Sampling

Matachewan

Certified by *Dennis Chant*

Matachewan Diamond Drilling Report

Appendix C

DDH Sections

- OPW-07-001; Section 600 E scale: 1:1500
- OPW-07-002; Section 400 E scale: 1:1500
- OPW-07-003; Section 400 W scale: 1:1500
- OPW-07-004, OPW-07-005; Section 400 E scale: 1:1500
- OPW-07-006, OPW-07-010; Section 600 W scale: 1:1500
- OPW-07-007; Section 200 E scale: 1:1500
- OPW-07-008; Section 200 E scale: 1:1500
- OPW-07-009; Section 200 W scale: 1:1500
- OPW-07-011; Section 200 W scale: 1:1500
- OPW-07-012; Section 600 W scale: 1:1500
- OPW-07-013; Section 400 W scale: 1:1500
- OPW-07-014; Section 600 W scale: 1:1500
- OPW-07-015; Section 600 W scale: 1:1500
- OPW-07-016; Section 200 W scale: 1:1500
- OPW-07-017; Section 400 W scale: 1:1500
- OPW-07-018; Section 600 W scale: 1:1500
- OPW-07-019; Section 850 W scale: 1:1500
- OPW-07-020; Section 00 scale: 1:1500
- OPW-07-021; Section 394 W scale: 1:2000
- OPW-07-022; Section 586 W scale: 1:1500

Maps

- Diamond Drill Hole Location Plan scale: 1:5000
- Compilation Plan Map scale: 1:5000
- Claim Map scale: 1:40000

-1600 m

-1500 m

-1400 m

-1300 m

OPW-07-001
Az: 330
Dip: -65



0 m

0 m

CAS
CGL

SILT

GW

SILT

SILT

SILT
LAMP

-100 m

-100 m

—● Opawica DDH 2007
— Au assay bar (>0.1 g/t)

UTM Zone 17 Nad 83
DDH E N
OPW-07-001 523073 5311704

-200 m

-200 m

SILT

SILT

GAB
GAB
SILT
SILT
QFP

SILT

CGL

-300 m

-300 m

SYN

CGL

LAM
LGM
LAM
CGL
LAM
LGM
LAM
CGL

0 1 2 3
Au g/t

600 m

-400 m

-400 m

MATACHEWAN PROJECT
Powell Twp., Northeastern Ontario

SECTION 600 E
with IP target
Looking WSW

Opawica Explorations Inc.



O|P|W
OPAWICA EXPLORATIONS INC.

Diamond Drill Hole
OPW-07-001

1:1500



September-04-08

-1600 m


-1500 m


-1400 m

-1300 m

-500 m

-500 m





Opawica DDH 2007
 Au assay bar (>0.1 g/t)

UTM Zone 17 Nad 83
 DDH E N
 OPW-07-003 521454 5312600

0 1 2 3
 Au g/t


MATACHEWAN PROJECT
 Powell Twp., Northeastern Ontario

SECTION 400 W
with IP target
Looking WSW

Opawica Explorations Inc.



OPIW
 OPAWICA EXPLORATIONS INC.
Diamond Drill Hole
OPW-07-003



September-04-08

-1500 m -1400 m -1300 m -1200 m

OPW-07-004
Az: 330
Dip: -60


OPW-07-005
Az: 330
Dip: -65



—●— Opawica DDH 2007
— Au assay bar (>0.1 g/t)

UTM Zone 17 Nad 83

DDH	E	N
OPW-07-004	522879	5311733
OPW-07-005	522799	5311863



MATACHEWAN PROJECT
Powell Twp., Northeastern Ontario

SECTION 400 E
with IP targets
Looking WSW

Opawica Explorations Inc.



Diamond Drill Holes
OPW-07-004 OPW-07-005

1:1500





September-04-08

-1500 m -1400 m -1300 m -1200 m

0 m
-100 m
-200 m
-300 m
-400 m
-500 m

0 m
-100 m
-200 m
-300 m
-400 m
-500 m






OPW-07-010
Az: 150
Dip: -50

OPW-07-006
Az: 150
Dip: -65

—●— Opawica DDH 2007
— Au assay bar (>0.1 g/t)

UTM Zone 17 Nad 83

DDH	E	N
OPW-07-006	521329	5312566
OPW-07-010	521383	5312327



MATACHEWAN PROJECT
Powell Twp., Northeastern Ontario

SECTION 600 W
with IP targets
Looking WSW

Opawica Explorations Inc.



O|P|W
OPAWICA EXPLORATIONS INC.

Diamond Drill Holes
OPW-07-006 OPW-07-010

1:1500



September-04-08

-1600 m

-1500 m

-1400 m



OPW-07-007
Az: 330
Dip: -50

OVB
DIA
GWE

DIA

GWE

GWE

MAF

GWE

FZ

GWE

MAF

SILT

—●— Opawica DDH 2007
— Au assay bar (>0.1 g/t)

UTM Zone 17 Nad 83

DDH	E	N
OPW-07-007	522717	5311594

0 m

0 m

-100 m


-100 m

-200 m

-200 m

-300 m

-300 m



201 m

MATACHEWAN PROJECT
Powell Twp., Northeastern Ontario

SECTION 200 E
with IP target
Looking WSW

Opawica Explorations Inc.



O|P|W
OPAWICA EXPLORATIONS INC.

Diamond Drill Hole
OPW-07-007

1:1500



September-04-08

-1600 m

-1500 m

-1400 m

-1300 m

-1200 m

-1100 m



OPW-07-008
Az: 330
Dip: -50

OVB
GWE
DIA
FP

SILT


FP

SILT

DIA

FZ

DIA



207

—● Opawica DDH 2007
— Au assay bar (>0.1 g/t)

UTM Zone 17 Nad 83

DDH E N
OPW-07-008 522625 5311771

0 m

0 m

-100 m

-100 m

-200 m

-200 m

-300 m

-300 m

-1300 m

-1200 m

-1100 m

MATACHEWAN PROJECT
Powell Twp., Northeastern Ontario

SECTION 200 E
with IP target
Looking WSW

Opawica Explorations Inc.



O|P|W
OPAWICA EXPLORATIONS INC.

Diamond Drill Hole
OPW-07-008

1:1500



September-04-08

300 m

400 m

500 m

0 m

0 m

-100 m

-100 m

-200 m

-200 m

-300 m

-300 m

300 m

400 m

500 m

NNW

OPW-07-009
Az: 330
Dip: -45

OVB
GWE

CGL

GWE

GWE

TALC

SYN

150 m



—●— Opawica DDH 2007
— Au assay bar (>0.1 g/t)

UTM Zone 17 Nad 83
DDH E N
OPW-07-009 521475 5312998

25

MATACHEWAN PROJECT
Powell Twp., Northeastern Ontario

SECTION 200 W
with IP target
Looking WSW


Opawica Explorations Inc.

1:1500

0 80 m

Diamond Drill Hole
OPW-07-009

September-04-08





MATACHEWAN PROJECT
Powell Twp., Northeastern Ontario

SECTION 200 W
with IP target
Looking WSW

Opawica Explorations Inc.



Diamond Drill Hole
OPW-07-011



● Opawica DDH 2007
 — Au assay bar (>0.1 g/t)

UTM Zone 17 Nad 83

DDH	E	N
OPW-07-013	521288	5312918

MATACHEWAN PROJECT
 Powell Twp., Northeastern Ontario

SECTION 400 W
 with IP target
 Looking WSW

Opawica Explorations Inc.



Diamond Drill Hole
OPW-07-013

1:1500




September-04-08


-900 m

-800 m

-700 m





SSE



OPW-07-014

Az: 150

Dip: -70

 Opawica DDH 2007
 Au assay bar (>0.1 g/t)

UTM Zone 17 Nad 83

DDH	E	N
OPW-07-014	521657	5311835

-100 m

-100 m

-200 m

-200 m

-300 m

-300 m

CGL

SYN

CGL

LAM
LAM
FP

CGL

SYN
CGL
SYN
GWE

300 m



MATACHEWAN PROJECT
 Powell Twp., Northeastern Ontario

SECTION 600 W
 with IP target
 Looking WSW

Opawica Explorations Inc.



O|P|W
 OPAWICA EXPLORATIONS INC.

Diamond Drill Hole
OPW-07-014

1:1500



September-04-08

-900 m

-800 m

-700 m

300 m

400 m

500 m



OPW-07-015
Az: 330
Dip: -60

OVB

DIA

MAF

DIA

MAF

DIA

GWE

201 m

—●— Opawica DDH 2007
 — Au assay bar (>0.1 g/t)

UTM Zone 17 Nad 83

DDH	E	N
OPW-07-015	521129	5312796



0 m

0 m

-100 m

-100 m

-200 m

-200 m

-300 m

-300 m

MATACHEWAN PROJECT
Powell Twp., Northeastern Ontario

SECTION 600 W
with IP target
Looking WSW

Opawica Explorations Inc.



O|P|W
OPAWICA EXPLORATIONS INC.

Diamond Drill Hole
OPW-07-15

1:1500




September-04-08

300 m

400 m


500 m



-600 m

-500 m

-400 m



OPW-07-016
Az: 150
Dip: -60

OVB

GWE

—● Opawica DDH 2007
— Au assay bar (>0.1 g/t)

UTM Zone 17 Nad 83

DDH	E	N
OPW-07-016	521820	5312371

CGL

GWE

GWE

CGL

GWE



GWE

CGL

GWE

CGL

DIA

300 m

MATACHEWAN PROJECT
Powell Twp., Northeastern Ontario

SECTION 200 W
with IP target
Looking WSW

Opawica Explorations Inc.



O|P|W
OPAWICA EXPLORATIONS INC.

Diamond Drill Hole
OPW-07-016

1:1500




September-04-08

-600 m

-500 m

-400 m



NNW

—●— Opawica DDH 2007
— Au assay bar (>0.1 g/t)

OPW-07-017
Az: 330
Dip: -50

UTM Zone 17 Nad 83

DDH E N
OPW-07-017 521912 5311782

0 1 2 3
Au g/t

MATACHEWAN PROJECT
Powell Twp., Northeastern Ontario

SECTION 400 W
with IP targets
Looking WSW

Opawica Explorations Inc.



O|P|W
OPAWICA EXPLORATIONS INC.

Diamond Drill Hole
OPW-07-017

September-04-08

-1300 m

-1200 m

-1100 m

OPW-07-018
Az: 330
Dip: -50



0 m

0 m

OVB
SILT
FP
SILT
ARG
SILT
FP
SILT
FZ

CGL

—●— Opawica DDH 2007
— Au assay bar (>0.1 g/t)

UTM Zone 17 Nad 83

DDH E N
OPW-07-018 521948 5311401

-100 m

-100 m

SILT

-200 m

-200 m

CGL



MAF
CGL
SILT

CGL

MAF

CGL

MAF

300 m

-300 m

-300 m

MATACHEWAN PROJECT
Powell Twp., Northeastern Ontario

SECTION 600 W
with IP target
Looking WSW

Opawica Explorations Inc.



O|P|W
OPAWICA EXPLORATIONS INC.

Diamond Drill Hole
OPW-07-018

1:1500




September-04-08

-1300 m

-1200 m

-1100 m



200 m 300 m 400 m 500 m

SSE 

OPW-07-019
Az: 150
Dip: -65

—●— Opawica DDH 2007
— Au assay bar (>0.1 g/t)

UTM Zone 17 Nad 83

DDH E N
OPW-07-019 520804 5312849

CAMKING ZONE

DIA

FZ
DIA
GWE
DIA
GWE
DIA

GWE

TALC

GWE

LAM

CKZ

LAM
ERZ

GWE

FP

GWE

DIA

GWE


DIA

CKZ

GWE

CKZ

600 m



O|P|W
OPAWICA EXPLORATIONS INC.

Diamond Drill Hole
OPW-07-019

MATACHEWAN PROJECT
Powell Twp., Northeastern Ontario

SECTION 850 W
Looking WSW

Opawica Explorations Inc.

1:1500



September-04-08

200 m 300 m 400 m 500 m

0 m
-100 m
-200 m
-300 m
-400 m
-500 m

0 m
-100 m
-200 m
-300 m
-400 m
-500 m

-1500 m

-1400 m

-1300 m



OPW-07-020
Az: 330
Dip: -50

0 m

0 m

QVR
Mafic
Cglt
FP
MAF
SILT
SILT
DIA
FP

0 1 2 3
Au g/t

—●— Opawica DDH 2007
— Au assay bar (>0.1 g/t)

UTM Zone 17 Nad 83

DDH E N
OPW-07-020 522569 5311483

-100 m

-100 m

FZ
SILT
FZ
DIA
SILT

-200 m

-200 m

DIA
SILT 300 m

-300 m

-300 m

MATACHEWAN PROJECT
Powell Twp., Northeastern Ontario

SECTION 00
with IP target
Looking WSW

Opawica Explorations Inc.



O|P|W
OPAWICA EXPLORATIONS INC.

Diamond Drill Hole
OPW-07-020

1:1500

0 80 m

September-04-08

-1500 m

-1400 m

-1300 m


-1600 m

-1500 m

-1400 m

-1300 m

-1200 m



OPW-07-021
 Az: 330
 Dip: -70



OVB

CGL

GWE

MAF

CGL

MAF

CGL

GWE

DIA

FZ

GWE

—●— Opawica DDH 2007
 — Au assay bar (>0.1 g/t)

UTM Zone 17 Nad 83

DDH	E	N
OPW-07-021	522170	5311303

DIA

CGL

DIA

SILT

FP

MAF

FP

MAF

SILT

FP

SILT

FP

702 m



MATACHEWAN PROJECT

Powell Twp., Northeastern Ontario

SECTION 394 W

with IP target

Looking WSW

Opawica Explorations Inc.



O|P|W
 OPAWICA EXPLORATIONS INC.

Diamond Drill Hole

OPW-07-021

1:2000



September-04-08

-1600 m

-1500 m

-1400 m

-1300 m

-1200 m

-700 m

-600 m

-500 m

-400 m

-300 m

-200 m

-100 m

0 m

-700 m

-600 m

-500 m

-400 m

-300 m


-200 m

-100 m

0 m


-1700 m -1600 m -1500 m -1400 m

OPW-07-022
Az: 330
Dip: -60



—●— Opawica DDH 2007
- - - Au assay bar (>0.1 g/t)

UTM Zone 17 Nad 83
DDH E N
OPW-07-022 522221 5311014



MATACHEWAN PROJECT
Powell Twp., Northeastern Ontario

SECTION 586 W
with IP target
Looking WSW

Opawica Explorations Inc.

1:1500

0 100 m


September-04-08



Diamond Drill Hole
OPW-07-022

-1700 m -1600 m -1500 m -1400 m


651 m



DDH-ID	Local Grid		UTM 17 Nad 83		Dip	Az	Length(m)
	E (m)	N (m)	E	N			
OPW-07-001	600E	1600S	523073	5311704	-65	330	600
OPW-07-002	400E	1645S	522948	5311612	-55	330	201
OPW-07-003	400W	030S	521454	5312600	-60	150	597
OPW-07-004	400E	1500S	522879	5311733	-60	330	600
OPW-07-005	400E	1350S	522799	5311863	-65	330	201
OPW-07-006	600W	0NS	521329	5312566	-65	150	432
OPW-07-007	200E	1540S	522717	5311594	-50	330	201
OPW-07-008	200E	1340S	522625	5311771	-50	330	201
OPW-07-009	200W	305N	521475	5312998	-45	330	150
OPW-07-010	600W	230S	521383	5312327	-50	150	201
OPW-07-011	200W	190N	521529	5312896	-60	150	351
OPW-07-012	600W	430S	521478	5312174	-55	150	300
OPW-07-013	400W	325N	521288	5312918	-57	150	252
OPW-07-014	600W	800S	521657	5311835	-70	150	300
OPW-07-015	600W	295N	521129	5312796	-60	330	201
OPW-07-016	200W	410S	521820	5312371	-60	150	300
OPW-07-017	400W	970S	521912	5311782	-50	330	498
OPW-07-018	600W	1300S	521948	5311401	-50	330	300
OPW-07-019	850W	500N	520804	5312849	-65	150	600
OPW-07-020	0EW	1550S	522569	5311483	-50	330	300
OPW-07-021	394W	1515S	522170	5311303	-70	330	702
OPW-07-022	586W	1737S	522221	5311014	-60	330	651


DDH Trace Opawica 2007
 1..22 Short Labels for OPW-07-001 to 022

OPAWICA EXPLORATIONS INC.
 Matatchewan Project
DIAMOND DRILL HOLE LOCATION PLAN
 OPW-07-001 TO OPW-07-022
 Powell Twp.
 Matatchewan Area, Northeastern Ontario



September-09-08

UTM Zone 17 N Nad 83



5313000 m

5312000 m

5311000 m

5310000 m

5313000 m

5312000 m

5311000 m

5310000 m

520000 m

521000 m

522000 m

523000 m

524000 m

520000 m

521000 m

522000 m

523000 m

524000 m

OPAWICA EXPLORATIONS INC.
Matachewan Project

COMPILATION PLAN MAP
GEOLOGY, DDH, TRENCH, AND GRID LOCATIONS

Powell Twp.
Matachewan, Ontario

UTM Zone 17N Nad 83
1:5000

September-10-08



alkaline intermediate and felsic intrusive rocks	Camking Zone	Titan Depth IP
alkaline mafic intrusive rocks	S2,S3,Hm+s	Titan Surface IP
clastic and chemical metasedimentary rocks - Archean	Collar OPW DDH	JVX IP Strong
felsic metavolcanic rocks	Trace OPW DDH	JVX IP Moderate
gowganda formation clastic metasedimentary rocks	Northgate DDH	JVX IP Weak
mafic metavolcanic rocks	Freewest DDH Trace	Freewest IP Strong
matachewan diabase	Sedex DDH	Freewest IP Moderate
ultramafic and mafic intrusive rocks	Opawica Trench	Freewest IP Weak
ultramafic metavolcanic rocks	Freewest Trench	
	Sedex Trench	

Ryan Lake Mine

Ryan Lake


Walker Zone Main Pit

Young Davidson Mine

MCM

Little Hawley Lake

Otisse Lake



0.78 g/t Au
(1.4 m)
0.89 g/t Au
(1.2 m)

1.42 g/t Au
(1 m)
1.22 g/t Au
(1.2 m)
1.78 g/t Au
(1 m)
2.32 g/t Au
(1 m)

0.33% Cu/0.32 g/t Au
(4.8 m)

2.46 g/t Au
(2.3 m)

2.74 g/t Au
(2 m)

WS 97-4

WS 96-2

WS 97-3

WS 96-1

WS 97-5

L 2W

L 0

L 2E

L 8W

L 7W

L 6W

L 5W

L 4E

L 6E

L 10W

L 9W

L 8W

L 7W

L 6E

L 4E

L 12W

L 11W

L 10W

L 9W

L 8W

L 7E

L 6E

L 14W

L 13W

L 12W

L 11W

L 10W

L 9W

L 8W

L 7E

L 6E

L 16W

L 15W

L 14W

L 13W

L 12W

L 11W

L 10W

L 9W

L 8W

L 18W

L 17W

L 16W

L 15W

L 14W

L 13W

L 12W

L 11W

L 10W

L 20W

L 19W

L 18W

L 17W

L 16W

L 15W

L 14W

L 13W

L 12W

L 22W

L 21W

L 20W

L 19W


L 18W

L 17W

L 16W

L 15W

L 14W



520000 m

525000 m



5315000 m


5315000 m

Matachewan Property

Opawica Explorations Inc.

**CLAIM MAP
MATACHEWAN PROPERTY**

**Powell Twp.
Larder Lake Mining Division
Ontario**



May-13-08

520000 m

525000 m

UTM Zone 17 Nad 83

5310000 m

5310000 m