

Opawica Explorations Inc.

Report

**Diamond Drilling
AT-08-001 to 009**

**Atikwa Lake Property
Atikwa Lake Twp
Kenora Mining Division
Ontario**

Table of Contents

Introduction.....	1
Property.....	1
Location and Access.....	3
Exploration History.....	3
Current Work.....	4
Diamond Drilling and Assaying.....	4
Results.....	5
References	8
Certificate of Qualifications.....	9

Illustration Index

Figure 1: Atikwa Lake Property Claims.....	2
Figure 2: Property Location.....	3

Appendices

Appendix A	
Core Logs	
Assay Certificates	
DDH Sections	
Maps	

Introduction

O pawica Explorations Inc. completed a diamond drill program of seventy drill holes during 2008 on the Atikwa Lake Property in North-western Ontario. This report covers the first nine drill holes (2,399.6 m) that tested IP anomalies and also the results of analysis of 1,518 core samples.


Property

The Atikwa Lake Property is comprised of 25 claims totalling 752 hectares. The claims are listed in Table 1 and shown in Figure 1.

Table 1: List of Claims

Claim #	Township	Claim #	Township
4204797	Atikwa Lake	K15374	Atikwa Lake
4204798	Atikwa Lake	K15375	Atikwa Lake
4224417	Atikwa Lake	K15376	Atikwa Lake
K15364	Atikwa Lake	K15377	Atikwa Lake
K15365	Atikwa Lake	K15378	Atikwa Lake
K15366	Atikwa Lake	K15379	Atikwa Lake
K15367	Atikwa Lake	K15380	Atikwa Lake
K15368	Atikwa Lake	K15381	Atikwa Lake
K15369	Atikwa Lake	K15524	Atikwa Lake
K15370	Atikwa Lake	K15525	Atikwa Lake
K15371	Atikwa Lake	K15526	Atikwa Lake
K15372	Atikwa Lake	K15527	Atikwa Lake
K15373	Atikwa Lake		

Figure 1: Atikwa Lake Property Claims




Location and Access

The Atikwa Lake property is located in Atikwa Lake Township in the Kenora Mining Division of North-western Ontario, and is 72 kilometres SE of the town of Kenora, and 33 kilometres E of the village of Sioux Narrows. The property is at Longitude 93.6519° W and Latitude 49.4210° N.

Access to the property is by Hwy 71 east-north-easterly from Sioux Narrows for 10 kilometres and then easterly along the Maybrun forest access road for 28.5 kilometres, and then east-north-easterly along the Maybrun mine access road for 1.5 kilometres to the Maybrun mine site.

Figure 2: Property Location



Exploration History

Date	Company	Description of Work	Diamond Drilling Drill Holes	Meters
1951	Noranda	Discovery, copper and gold.		
1951-53	Noranda	Prospecting & Diamond drilling, established the presence of copper-gold mineralization over a strike length of about 3,000 feet (900m).		10,670
1954	Noranda	Outlined two potential ore bodies (B & Ross Zone).		
1955-57	Maybrun	As of June 1957 diamond drilling on surface over 66,000		20,135

Date	Company	Description of Work	Diamond Drilling Drill Holes	Meters
		feet was completed. A 298 Foot shaft was sunk and two levels were developed on 150 ft. and 275 ft. horizon and diamond drilling continued from underground. The exploration program indicated and blocked out 2,824,835 tonnes with a grade of 1.18% copper and 0.08 ounces per ton gold.		8,438
1965	Maybrun	The property was reassessed under new Management.		
1969	Maybrun	Plans for an open pit mine were established and additional claims staked.		
1970	Maybrun	Construction of a 500-ton mill was commenced followed by open pit mining. Field observations indicate that some 200,000 tons were removed from the pit prior to closing the mine and placing it on care and maintenance. Local workers from the mine recall that the concentrate was shipped by barge and overland for processing.		
		Total Historical Diamond Drilling		39,243
Oct 2005	Opawica	Diamond Drill Program Phase I.	OPW 1 to 18	2,962
Jan 2006		Exploration and diamond drilling confirmed previous activities and values during the 1955 to 1970 work.		
Feb 2006	Opawica	Down Hole Geophysics on holes 4, 6, and 3.		
Jul 2006	Opawica	Diamond Drill Program Phase II.	OPW 20 to 32	1,812
Sep 2006		Geological Studies and Exploration.		
Apr 2007	Opawica	Diamond Drill Program Phase III.	OPW 33 to 35	549
May 2007		Geological Studies and Exploration.		
Aug 2007	Opawica	Diamond Drill Program Phase IV.	OPW 36 & 37	440
Oct 2007	Opawica	Compilation of all Historic Data, both surface and underground.		
Nov 2007	Opawica	Deep IP Geophysics (Insight); Lines 500N -1300N.		
Jan 2008	Opawica	Drill hole information completed on SECTIONS.		
Jan 2008	Opawica	Deep IP Geophysics; Lines 1400N -2200N @ 100m lines.		
Jan 2008	Opawica	Interpretation of Geology 90% complete. Building a data base for a 3-D Resource Model, on going into March, 2008.		
Mar 2008	Opawica	Magnetometer Survey over Property along 100m lines. Deep IP Geophysics; Lines 500N -1350N (50m intervals).		
Jan to Aug '08	Opawica	Diamond Drill Program Phase V.	AT 1 to 70	13,200
		Total Opawica Diamond Drilling		18,963
		TOTAL DIAMOND DRILLING METERS		58,206

Current Work

Diamond Drilling and Assaying

Opawica completed a program of diamond drilling and assaying during 2008 on the Atikwa Lake Property. Seventy diamond drill holes were drilled totalling 13,200 metres. This report covers the first nine diamond drill holes labelled

AT-08-001 to AT-08-009 totalling 2,399.6 metres that were drilled from January 15 to February 22, 2008. One thousand five hundred and eighteen core samples were assayed for gold and copper ± silver from February 6 to April 3, 2008.

The work was supervised by the following personnel:

Fred Kiernicki of Kirkland Lake, Ontario

Kevin O'Flaherty of Kenora, Ontario

The drilling was carried out by Downing Drilling Limited of Grenville-Sur-La-Rouge, (Québec), using a Longyear model LF70 diamond drill equipped with NQ drill tools. A Caterpillar D6 bulldozer was used for site preparation and drill moves. The drill was operated 24 hours per day with shifts of 12 hours and 2 men per shift with Opawica personnel on site during the day to oversee the drilling. The core was transported to Opawica's core logging facilities in Matachewan, Ontario, where it was logged and sampled. Geologist Fred Sharpley of Kirkland Lake logged the core and supervised the core sawing and sampling. Opawica inserted standards every twenty samples, and also duplicates and blanks every twenty samples to check the analytical accuracy. Assaying was completed by Swastika Laboratories Ltd., of Swastika, Ontario.

Table 2: DDH Locations

DDH ID	Local Grid		UTM Zone 15 Nad 83					
	Northing (m)	Easting (m)	Northing	Easting	Elevation (m)	Azimuth	Dip	EOH (m)
AT-08-001	1200	2070	5474669	452738	410	270	-50	222
AT-08-002	1200	2255	5474664	452920	387	90	-45	201
AT-08-003	1000	2250	5474463	452905	400	90	-45	240
AT-08-004	1000	2250	5474463	452904	400	270	-45	398.6
AT-08-005	1200	2477	5474657	453144	368	90	-45	147
AT-08-006	1200	2575	5474655	453242	382	90	-45	162
AT-08-007	1000	2465	5474456	453117	382	90	-45	252
AT-08-008	800	2275	5474260	452929	399	90	-45	351
AT-08-009	700	2265	5474150	452914	396	90	-45	426

Results

AT-08-001 was drilled to test an Insight IP anomaly with strong chargeability and low resistivity on the northern end of the Ross Zone. Massive andesite flows, pillow flows, and feldspar porphyry were penetrated. Chalcopyrite and pyrrhotite occur in pillow selvages and fractures with stronger mineralization in the upper part of the hole. The hole ended in mineralization. Highest assay of 22.29 g/t Au and 8.56% Cu over 1 metre is within a composite assay of 1.54 g/t Au and 0.393% Cu over 183 metres which includes 10.24 g/t Au and 2.396% Cu over 9 metres core length. True widths in this hole are estimated to be 30% of core lengths.

AT-08-002 was drilled to test an Insight IP anomaly with strong chargeability and low resistivity and penetrated mafic flows/mafic flow breccia mineralized with up to 1% pyrrhotite, and feldspar porphyry dykes. Highest assay was 0.55 g/t Au and 0.139% Cu over 0.43 metres.

AT-08-003 was drilled to test Insight IP anomalies with strong chargeability and low resistivities at the north end of the Discovery Zone. Mafic flows/mafic flow breccia with up to 5% pyrrhotite, and feldspar porphyry were encountered.

Highest assay of 4.83 g/t Au and 0.017% Cu over 0.45 metres occurs within a wider composite of 0.45 g/t Au and 0.017% Cu over 17.5 metres.

AT-08-004 was drilled to test Insight IP anomalies with moderate chargeability and low resistivities at depth below the underground workings within the B Zone. Mafic flows, pillow flows, dacite, and feldspar porphyry were penetrated. Pyrrhotite and chalcopyrite ± pyrite occur within pillow selvages in the upper part of the hole and in altered mafic flows and in dacite with quartz veinlets near the end of the hole. Highest assay of 11.73 g/t Au and 0.022% Cu over 1 metre is within a composite of 0.60 g/t Au and 0.131% Cu over 30 metres from 364 to 394 metres. This hole was drilled from east to west, probably down dip at a low angle to the B zone and may not have completely cut the target anomalies.

AT-08-005 was drilled to test an Insight IP anomaly with strong chargeability and low resistivity at the Portage Zone. Mafic flows, diorite, and feldspar porphyry were cut with sections mineralized with up to 3% disseminated pyrrhotite and chalcopyrite. Highest assay of 4.15 g/t Au and 0.343% Cu over 1 metre is within a composite of 3.26 g/t Au and 0.426% Cu over 2 metres.

AT-08-006 was drilled to test an Insight IP anomaly with strong chargeability and moderate to high resistivity east of the Portage Zone. Diorite, mafic flows, feldspar porphyry, gabbro, and fault zones were penetrated. A section from 60 to 67 metres is mineralized with 1 % pyrite. No significant assays were reported.

AT-08-007 was drilled to test Insight IP anomalies with strong chargeability and low resistivity. Mafic flows, diorite, gabbro, felsic tuff, and feldspar porphyry were cut with wide intervals mineralized with up to 3% pyrrhotite. Highest assay of 3.05 g/t Au and 0.258% Cu over 1.1 metre is within a composite of 1.12 g/t Au and 0.124% Cu over 6.4 metres.

AT-08-008 was drilled to test Insight IP anomalies with strong chargeability and low resistivity at the south end of the B Zone. Pillowed flows, mafic flows ± vesicles, mafic flow breccia, diorite, feldspar porphyry, and fault zones were penetrated. Pyrrhotite and chalcopyrite mineralization is present in pillow selvages, fractures, vesicles, and in breccia matrix. Highest assay of 7.75 g/t Au and 0.477% Cu is within a composite of 2.89 g/t Au and 0.199% Cu over 5 metres.

AT-08-009 was drilled to test Insight IP anomalies with strong chargeability and low resistivity. Pillowed flows, mafic flows ± vesicles, mafic flow breccia, diorite, diabase, feldspar porphyry, and fault zones were penetrated. Pyrrhotite and chalcopyrite mineralization is present in pillow selvages, fractures, vesicles, and in breccia matrix. Highest assay of 3.91 g/t Au and 0.130% Cu over 0.5 metre is within a composite of 2.60 g/t Au and 0.391% Cu over 1.5 metres.

Composite assays are shown in Table 3 below. Drill hole logs with assays, assay certificates, drill hole sections and maps are included in Appendix A.

Table 3: Composite Assays

Hole No.	Section	Target		From	To	Width	Gold (g/t)			
				(m)	(m)	(m)	Cut to 30 g/t	Uncut	Cu %	
AT-08-001	1200 N	Maybrun		39.00	222.00	183.00		1.54	1.54	0.393
				including	41.25	157.00	115.75	2.40	2.40	0.517
				including	41.25	88.00	46.75	4.02	4.02	0.866
				including	60.00	87.00	27.00	6.43	6.43	1.317
				including	65.00	74.00	9.00	10.24	10.24	2.396
				and	94.40	108.00	13.60	4.71	4.71	0.790
AT-08-002	1200 N	IP			42.94	49.50	6.56	0.13	0.13	0.036
					149.57	150.00	0.43	0.55	0.55	0.139
					160.00	161.90	1.90	0.18	0.18	0.047
AT-08-003	1000 N	IP			78.50	96.00	17.50	0.45	0.45	0.017
				including	91.00	91.45	0.45	4.83	4.83	0.017
					112.00	113.00	1.00	1.09	1.09	0.015
					175.20	176.00	0.80	1.29	1.29	0.155
AT-08-004	1000 N	IP			200.00	203.00	3.00	0.40	0.40	0.359
					267.00	268.00	1.00	2.61	2.61	0.008
					292.00	314.00	22.00	0.21	0.21	0.192
				including	364.00	394.00	30.00	0.60	0.60	0.131
					383.00	384.00	1.00	11.73	11.73	0.022
AT-08-005	1200 N	IP			20.00	22.00	2.00	3.26	3.26	0.426
					66.00	78.00	12.00	0.24	0.24	0.193
AT-08-006	1200 N	IP			62.00	64.00	2.00	0.10	0.10	0.057
AT-08-007	1000 N	IP			18.00	33.00	15.00	0.57	0.57	0.035
				including	27.00	28.00	1.00	3.77	3.77	0.058
					59.60	66.00	6.40	1.12	1.12	0.124
				including	64.00	65.10	1.10	3.05	3.05	0.258
AT-08-008	800 N	Maybrun			*6.00	14.00	8.00	1.99	1.99	0.142
				including	*9.00	14.00	5.00	2.89	2.89	0.199
					73.00	74.00	1.00	2.30	2.30	0.052
					113.00	124.00	11.00	0.41	0.41	0.327
					198.00	200.00	2.00	2.86	2.86	0.261
AT-08-009	700 N	IP			331.00	342.00	11.00	0.31	0.31	0.044
				including	341.00	342.00	1.00	1.85	1.85	0.036
					373.00	374.50	1.50	2.60	2.60	0.391

References

- Davies, J.C. 1973: Geology of the Atikwa Lake Area, District of Kenora; Ontario Div. Mines, GR 111, 57p. Accompanied by map 2273, scale 1 inch to $\frac{1}{2}$ mile.
- Laakso, R.W., O'Flaherty, K.F. 2005: Technical Report on the Atikwa Lake Cu, Au Property in District of Kenora for Opawica Explorations Inc.
- Matthews, H.L., 1984: Geological Report on the Maybrun Mine Property, Kenora Mining District.
- Montgomery, H.B. 1957: Geology of the Maybrun Mines Property, Kenora District, Ontario; Thesis, M.Sc., Pennsylvania State University.
- Setterfield, T.N. 1980: Petrology and Chemistry of Pillowed Metabasalts and their Copper Mineralization, Maybrun Mine, Ontario; Thesis, B.Sc., Carleton University.

Certificate of Qualifications

I, Terry Arnold Link of the Town of Kirkland Lake, Province of Ontario, do hereby certify:

- 1) That I am an independent prospector and exploration contractor and reside at 13 Government Road West, Apartment # 9, P.O. Box 561, Kirkland Lake, Ontario, P2N 3J5.
- 2) That I completed—with a 4.0 GPA—the first year of the Mining Engineering Technology course at the Haileybury School of Mines, Haileybury, Ontario. (1993)
- 3) That I have worked in the field of mineral exploration as an independent prospector and exploration contractor over the past 14 years and prior to 1993 prospected part time over a period of 15 years.
- 4) That I wrote the report.

Dated at Kirkland Lake, Ontario on October 29, 2008

Terry A. Link

Appendix A

Core Logs

- AT-08-001
- AT-08-002
- AT-08-003
- At-08-004
- AT-08-005
- AT-08-006
- AT-08-007
- AT-08-008
- AT-08-009

Assay Certificates

8W-0260-RA1	8W-0367-RA1	8W-0615-RA1
8W-0261-RA1	8W-0368-RA1	8W-0616-RA1
8W-0262-RA1	8W-0448-RA1	8W-0619-RA1
8W-0263-RA1	8W-0449-RA1	8W-0620-RA1
8W-0285-RA1	8W-0458-RA1	8W-0667-RA1
8W-0297-RA1	8W-0459-RA1	8W-0668-RA1
8W-0298-RA1	8W-0477-RA1	8W-0669-RA1
8W-0350-RA1	8W-0478-RA1	8W-0715-RA1
8W-0351-RA1	8W-0544-RA1	8W-0716-RA1
8W-0352-RA1	8W-0545-RA1	8W-0717-RA1
8W-0353-RA1	8W-0598-RA1	8W-0718-RA1
8W-0366-RA1	8W-0599-RA1	

DDH Sections

- Section 1200 N; DDH's AT-08-001 and 002 scale: 1:1,500
- Section 1200 N; DDH's AT-08-005 and 006 scale: 1:1,000
- Section 1000 N; DDH's AT-08-003 and 004 scale: 1:1,500
- Section 1000 N; DDH's AT-08-003 and 007 scale: 1:1,500
- Section 800 N; DDH AT-08-008 scale: 1:1,500
- Section 700 N; DDH AT-08-009 scale: 1:1,500

Maps

- DDH Locations AT-08-001 to 009 scale: 1:5,000
- Atikwa Lake Property Claim Map scale: 1:30,000

Opawica Explorations Inc.

Atikwa Property UTM GRID LOCATION: Atikwa Lake Area, Ontario
 DDH#: AT-08-001 452738.44 E DRILL COMPANY: DOWNING
 Az 270.00 5474669.17 N GRID: Local, Metric:
 DIP -50.00 ZONE 15 E 2070.00
 E.O.H: 222 m NAD 83 N 1200.00
 Elev.: 409.76 Start: January 15, 2008; End: January 17, 2008

DDH#: AT-08-001

Drill Company: Claim: K15375
 Downing: NQ Core
 Logged by: FRED SHARPLEY

From	To (m)	Rock Type	Code	Description	Fred Sharpley							
					Sample#	From	To	Width	Au g/t	Au2 g/t	Ag g/t	Cu %
0.00	3.20	OVBD										
3.20	4.80	MF		Massive Spotted Andesite: dark green, very fine grained, massive uniform, scattered 1 cm feldspathic spots, irregular boundary								
4.80	7.40	FP		Feldspar Porphyry: light greyish, fine grained feldspathic matrix with medium grained feldspar phenocrysts, massive, uniform, contact at 45 CA								
7.40	23.20	MF		as above: spotted								
				9.2 trace pyrrhotite in qcv								
				11.2 trace po in qcv at low angle								
				13.1 traces po, cpy in qcv at 45 CA								
23.20	24.30	FP		as above:								
24.30	41.25	MF		as above: spotted								
				29.6-30.2 traces po, cpy in qcv								
				36.6 traces po, cpy in qcv								
41.25	88.00	PF		Pillowed Flow: dark green, very fine grained, numerous quartz carbonate veins, pillowed salvage with po, cpy; spotted with feldspar	49001	39.00	40.00	1.00	0.08	-	0.20	0.049
					49002	40.00	40.50	0.50	0.005	-	0.20	0.013
					49003	40.50	41.25	0.75	0.01	-	0.20	0.030
					49004	41.25	42.00	0.75	0.29	-	0.80	0.260
					49005	42.00	43.00	1.00	0.02	-	0.90	0.438
					49006	43.00	44.00	1.00	0.31	-	0.40	0.162
					49007	44.00	45.00	1.00	0.19	-	0.20	0.033
					49008	45.00	46.00	1.00	3.84	4.73	0.30	0.119
					49009	46.00	47.00	1.00	0.25	-	0.50	0.155
					49010	Standard	53Pb		0.61	-	1.70	0.540

From	To (m)	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Ag g/t	Cu %
					49011	47.00	48.00	1.00	2.55	-	1.50	0.650
					49012	48.00	49.00	1.00	0.11	-	0.20	0.026
					49013	49.00	50.00	1.00	0.07	-	0.20	0.069
					49014	50.00	51.00	1.00	0.16	-	1.00	0.387
					49015	51.00	52.00	1.00	0.005	-	0.10	0.011
					49016	52.00	53.00	1.00	0.30	-	1.50	0.454
					49017	53.00	54.00	1.00	1.30	2.38	1.70	0.640
					49018	54.00	55.00	1.00	0.15	-	0.60	0.216
					49019	Dup			0.12	-	0.50	0.205
					49020	Blank			0.005	-	0.10	0.005
					49021	55.00	56.00	1.00	0.62	-	1.70	0.700
					49022	56.00	57.00	1.00	0.23	-	0.20	0.069
					49023	57.00	58.00	1.00	0.03	-	0.10	0.003
					49024	58.00	59.00	1.00	2.82	-	0.50	0.235
					49025	59.00	60.00	1.00	0.89	-	0.60	0.309
					49026	60.00	61.00	1.00	4.11	-	1.20	0.680
					49027	61.00	62.00	1.00	8.09	8.09	1.60	0.880
					49028	62.00	63.00	1.00	5.01	-	2.20	1.210
					49029	63.00	64.00	1.00	6.00	-	2.00	1.020
					49030	Standard	54Pa		2.84	-	4.50	1.480
					49031	64.00	65.00	1.00	8.57	7.61	1.00	0.493
					49032	65.00	66.00	1.00	13.44	-	3.40	3.630
					49033	66.00	67.00	1.00	14.98	13.30	3.50	1.770
					49034	67.00	68.00	1.00	8.81	-	4.30	1.750
					49035	68.00	69.00	1.00	2.71	-	1.30	0.720
					49036	69.00	70.00	1.00	3.98	-	1.90	0.940
					49037	70.00	71.00	1.00	10.29	-	1.80	0.940
					49038	71.00	72.00	1.00	6.03	-	3.70	1.600
					49039	Dup			5.31	-	3.20	1.540
					49040	Blank			0.01	-	0.10	0.008
					49041	72.00	73.00	1.00	9.60	-	4.20	1.660
					49042	73.00	74.00	1.00	22.29	25.78	15.20	8.560
					49043	74.00	75.00	1.00	1.44	-	2.40	1.050
					49044	75.00	76.00	1.00	1.15	-	1.70	0.790
					49045	76.00	77.00	1.00	0.12	-	0.10	0.020
					49046	77.00	78.00	1.00	0.15	-	0.10	0.013
					49047	78.00	79.00	1.00	6.58	-	0.60	0.282
					49048	79.00	80.00	1.00	1.91	-	1.40	0.550
					49049	80.00	81.00	1.00	1.98	-	0.50	0.216
					49050	Standard	SE 29		0.58	-	0.90	0.001
					49051	81.00	82.00	1.00	6.79	-	3.20	1.690
					49052	82.00	83.00	1.00	7.75	7.68	2.80	1.090
					49053	83.00	84.00	1.00	3.05	-	1.20	0.465

From	To (m)	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Ag g/t	Cu %
					49054	84.00	85.00	1.00	0.12	-	0.10	0.022
					49055	85.00	86.00	1.00	2.95	-	1.40	0.500
					49056	86.00	87.00	1.00	15.77	15.98	5.10	3.030
					49057	87.00	88.00	1.00	0.23	-	0.30	0.048
88.00	94.40	FP		Feldspar Porphyry: light grey, fine grained with fine grained white feldspar phenocrysts, massive uniform, sharp contact at 20 CA	49058	88.00	89.00	1.00	0.04	-	0.20	0.021
					49059	Dup			0.01	-	0.20	0.009
				90.85-71.7 MF	49060	Blank			0.005	-	0.10	0.002
					49061	89.00	90.00	1.00	0.005	-	0.10	0.006
					49062	90.00	90.85	0.85	0.005	-	0.10	0.008
					49063	90.85	91.70	0.85	0.005	-	0.10	0.003
					49064	91.70	92.50	0.80	0.01	-	0.20	0.007
					49065	92.50	93.50	1.00	0.02	-	0.10	0.008
					49066	93.50	94.40	0.90	0.02	-	0.10	0.006
94.40	96.60	MF		as above: spotted	49067	94.40	95.00	0.60	4.77	5.21	1.40	0.610
					49068	95.00	96.00	1.00	5.76	5.07	3.00	1.550
					49069	96.00	96.60	0.60	1.60	-	0.40	0.096
					49070	Standard	53Pb		0.63	-	1.80	0.550
96.60	98.50	FP		as above	49071	96.60	97.50	0.90	0.09	-	0.10	0.020
					49072	97.50	98.50	1.00	0.07	-	0.20	0.031
98.50	104.30	MF		as above	49073	98.50	99.00	0.50	27.77	30.86	7.10	4.320
					49074	99.00	100.00	1.00	0.80	-	0.70	0.225
					49075	100.00	101.00	1.00	0.61	-	0.70	0.334
					49076	101.00	102.00	1.00	8.78	4.94	3.10	1.350
					49077	102.00	103.00	1.00	3.43	-	1.60	0.720
					49078	103.00	103.50	0.50	0.98	-	1.90	1.030
					49079	Dup			0.88	-	2.10	1.000
					49080	Blank			0.01	-	0.10	0.009
					49081	103.50	104.30	0.80	17.14	18.51	2.70	1.140
104.30	105.50	FP		as above	49082	104.30	105.00	0.70	0.36	-	0.20	0.034
105.50	118.10	MF		Spotted Massive Flow: as above	49083	105.00	105.50	0.50	0.12	-	0.10	0.028
					49084	105.50	107.00	1.50	7.06	4.66	2.50	0.800
					49085	107.00	108.00	1.00	1.66	-	3.10	1.270
					49086	108.00	109.00	1.00	0.02	-	0.10	0.010
					49087	109.00	110.00	1.00	0.005	-	0.20	0.014
					49088	110.00	111.00	1.00	0.41	-	2.80	0.085
					49089	111.00	112.00	1.00	0.40	-	0.30	0.062
					49090	Standard	54Pa		2.88	-	4.70	1.470
					49091	112.00	113.00	1.00	0.31	0.48	0.30	0.069
					49092	113.00	114.00	1.00	0.69	-	0.80	0.332
					49093	114.00	115.00	1.00	3.05	-	1.40	0.640
					49094	115.00	116.00	1.00	0.59	-	0.30	0.118

From	To (m)	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Ag g/t	Cu %
					49095	116.00	117.00	1.00	0.06	-	0.10	0.011
					49096	117.00	117.50	0.50	0.04	-	0.10	0.016
					49097	117.50	118.10	0.60	0.08	-	0.30	0.073
118.10	121.50	FP		as above	49098	118.10	119.00	0.90	0.12	-	0.40	0.130
					49099	Dup			0.14	-	0.30	0.155
					49100	Blank			0.005	-	0.10	0.002
					49101	119.00	120.00	1.00	0.39	-	0.30	0.127
					49102	120.00	121.00	1.00	0.04	0.03	0.10	0.022
					49103	121.00	121.50	0.50	0.09	-	0.20	0.029
121.50	133.80	MF		Spotted Massive Flow: as above	49104	121.50	122.00	0.50	0.26	-	0.40	0.240
					49105	122.00	123.00	1.00	1.83	-	1.00	0.500
					49106	123.00	124.00	1.00	0.05	-	0.20	0.018
					49107	124.00	125.00	1.00	3.91	5.55	3.00	1.300
					49108	125.00	126.00	1.00	1.03	-	1.10	0.510
					49109	126.00	127.00	1.00	0.52	-	2.10	1.010
					49110	Standard	SE 29		0.57	-	0.90	0.001
					49111	127.00	128.00	1.00	0.54	-	0.20	0.028
					49112	128.00	129.00	1.00	0.29	-	0.30	0.128
					49113	129.00	130.00	1.00	0.12	-	0.40	0.143
					49114	130.00	131.00	1.00	0.005	-	0.10	0.009
					49115	131.00	132.00	1.00	0.01	-	0.10	0.009
					49116	132.00	133.00	1.00	0.20	-	1.20	0.420
					49117	133.00	133.80	0.80	0.60	-	1.80	0.680
133.80	138.95	FP		as above	49118	133.80	134.50	0.70	0.02	-	0.10	0.019
					49119	Dup			0.005	-	0.10	0.018
					49120	Blank			0.005	-	0.10	0.002
					49121	134.50	135.00	0.50	0.03	-	0.10	0.025
					49122	135.00	136.00	1.00	2.47	2.49	0.90	0.178
					49123	136.00	137.00	1.00	0.11	-	0.20	0.056
					49124	137.00	138.00	1.00	0.005	-	0.30	0.087
					49125	138.00	138.95	0.95	0.05	-	0.30	0.029
138.95	143.90	MF		as above: rare pillow: spotted	49126	138.95	139.50	0.55	0.01	-	0.10	0.010
					49127	139.50	140.00	0.50	0.02	-	0.20	0.024
					49128	140.00	141.00	1.00	0.01	-	0.10	0.011
					49129	141.00	142.00	1.00	0.005	-	0.10	0.018
					49130	Standard	53Pb		0.60	-	1.70	0.550
					49131	142.00	143.00	1.00	0.03	0.01	0.10	0.017
					49132	143.00	143.90	0.90	0.02	-	0.20	0.021
143.90	148.70	FP		as above	49133	143.90	144.40	0.50	0.01	-	0.10	0.018
					49134	144.40	145.00	0.60	0.02	-	0.20	0.035
					49135	145.00	146.00	1.00	0.06	-	0.90	0.152
					49136	146.00	147.00	1.00	0.05	-	0.20	0.090
					49137	147.00	148.00	1.00	0.01	-	0.10	0.008

From	To (m)	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Ag g/t	Cu %
					49138	148.00	148.70	0.70	1.05	1.41	8.80	0.035
					49139	Dup			2.57	2.43	9.60	0.027
					49140	Blank			0.02	-	0.10	0.002
148.70	169.00	MF		as above: rare pillow: spotted	49141	148.70	149.50	0.80	0.29	-	4.00	0.007
					49142	149.50	150.00	0.50	0.03	-	1.00	0.089
					49143	150.00	151.00	1.00	0.05	-	0.60	0.123
					49144	151.00	152.00	1.00	0.10	-	0.50	0.086
					49145	152.00	153.00	1.00	0.45	-	0.80	0.135
					49146	153.00	154.00	1.00	1.92	-	2.30	0.088
					49147	154.00	155.00	1.00	0.08	-	0.80	0.162
					49148	155.00	156.00	1.00	3.50	3.70	2.30	0.610
					49149	156.00	157.00	1.00	0.28	0.18	0.70	0.178
					49150	Standard	54Pa		2.72	-	4.80	1.450
					49151	157.00	158.00	1.00	0.01	-	0.10	0.002
					49152	158.00	159.00	1.00	0.07	0.34	0.30	0.040
					49153	159.00	160.00	1.00	0.01	-	0.20	0.027
					49154	160.00	161.00	1.00	0.13	-	0.90	0.304
					49155	161.00	162.00	1.00	0.05	-	0.70	0.227
					49156	162.00	163.00	1.00	0.11	-	2.20	0.590
					49157	163.00	164.00	1.00	0.03	-	0.40	0.110
					49158	164.00	165.00	1.00	0.005	-	0.10	0.013
					49159	Dup			0.005	-	0.10	0.022
					49160	Blank			0.005	-	0.10	0.001
					49161	165.00	166.00	1.00	0.005	-	0.20	0.039
					49162	166.00	167.00	1.00	0.005	-	0.10	0.020
					49163	167.00	168.00	1.00	0.005	-	0.10	0.008
					49164	168.00	169.00	1.00	0.005	-	0.10	0.003
169.00	177.40	MF		as above: spotted	49165	169.00	170.10	1.10	0.005	-	0.10	0.007
					49166	170.10	171.00	0.90	0.005	-	0.10	0.005
					49167	171.00	172.00	1.00	0.14	0.16	1.40	0.153
					49168	172.00	173.00	1.00	0.005	-	0.60	0.108
					49169	173.00	174.00	1.00	0.005	-	0.20	0.029
					49170	Standard	SE 29		0.58	-	0.80	0.001
					49171	174.00	175.00	1.00	0.005	-	0.10	0.015
					49172	175.00	176.00	1.00	0.24	-	1.20	0.225
					49173	176.00	177.00	1.00	0.005	-	0.10	0.001
					49174	177.00	177.40	0.40	0.005	-	0.10	0.001
177.40	180.90	FP		as above: contact at 20-30 CA	49175	177.40	178.00	0.60	0.01	-	0.10	0.010
					49176	178.00	179.00	1.00	0.005	0.005	0.100	0.006
					49177	179.00	180.00	1.00	0.005	-	0.10	0.009
					49178	180.00	180.90	0.90	0.005	-	0.20	0.006
					49179	Dup			0.01	-	0.10	0.007
					49180	Blank			0.005	-	0.10	0.001

From	To (m)	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Ag g/t	Cu %
180.90	205.54	MF		as above: spotted	49181	180.9	181.50	0.60	0.005	-	0.10	0.012
					49182	181.5	182.00	0.50	0.01	-	0.80	0.144
					49183	182.0	183.00	1.00	0.005	-	0.60	0.158
					49184	183.0	184.00	1.00	0.03	-	0.50	0.129
					49185	184.0	185.00	1.00	0.005	-	0.10	0.007
					49186	185.0	186.00	1.00	0.01	0.005	0.100	0.016
					49187	186.0	187.00	1.00	0.01	-	0.10	0.020
					49188	187.0	188.00	1.00	0.24	-	3.90	0.471
					49189	188.0	189.00	1.00	0.06	-	1.30	0.257
					49190	Standard	53Pb		0.63	-	1.70	0.550
					49191	189.00	190.00	1.00	0.41	-	1.10	0.436
					49192	190.00	191.00	1.00	0.005	-	0.10	0.004
					49193	191.00	192.00	1.00	0.11	-	1.00	0.336
					49194	192.00	193.00	1.00	0.07	-	0.30	0.080
					49195	193.00	194.00	1.00	0.50	0.57	4.70	1.530
					49196	194.00	195.00	1.00	0.005	-	0.10	0.032
					49197	195.00	196.00	1.00	0.38	-	4.70	1.470
					49198	196.00	197.00	1.00	0.005	-	0.10	0.003
					49199	Dup			0.01	-	0.10	0.002
					49200	Blank			0.005	-	0.10	0.001
					49201	197.00	198.00	1.00	0.005	-	0.20	0.017
					49202	198.00	199.00	1.00	0.03	-	0.70	0.071
					49203	199.00	200.00	1.00	0.11	-	1.00	0.304
					49204	200.00	201.00	1.00	0.08	-	0.40	0.118
					49205	201.00	202.00	1.00	0.07	-	0.60	0.122
					49206	202.00	203.00	1.00	0.15	-	1.20	0.255
					49207	203.00	204.00	1.00	0.05	0.02	0.30	0.046
					49208	204.00	205.00	1.00	0.005	-	0.10	0.005
					49209	205.00	205.54	0.54	0.08	-	0.90	0.250
					49210	Standard	54Pa		2.71	-	4.90	1.470
205.54	210.20	FP		as above: contact at 20 CA	49211	205.54	206.00	0.46	0.28	-	5.30	1.290
					49212	206.00	206.40	0.40	0.09	-	1.00	0.237
					49213	206.40	207.00	0.60	0.03	-	0.90	0.082
					49214	207.00	208.00	1.00	0.005	-	0.20	0.014
					49215	208.00	209.00	1.00	0.01	-	0.30	0.036
					49216	209.00	209.50	0.50	0.005	-	0.70	0.008
					49217	209.50	210.20	0.70	0.005	-	0.30	0.008
210.20	222.00	MF		as above: spotted	49218	210.20	211.00	0.80	0.04	-	0.80	0.134
					49219	Dup			0.04	-	1.00	0.133
				212.6-212.9 FP	49220	Blank			0.005	-	0.10	0.001
					49221	211.00	212.00	1.00	0.005	-	0.10	0.001
					49222	212.00	213.00	1.00	0.005	0.005	0.100	0.004
					49223	213.00	214.00	1.00	0.005	-	0.10	0.002

From	To (m)	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Ag g/t	Cu %
					49224	214.00	215.00	1.00	0.005	-	0.10	0.001
					49225	215.00	216.00	1.00	0.35	0.48	3.90	1.160
					49226	216.00	217.00	1.00	0.02	-	0.10	0.009
					49227	217.00	218.00	1.00	0.57	0.41	4.50	1.250
					49228	218.00	219.00	1.00	0.09	-	1.70	0.446
					49229	219.00	220.00	1.00	0.005	-	0.40	0.050
					49230	Standard	SE 29		0.60	-	0.90	0.002
					49231	220.00	221.00	1.00	0.005	-	0.10	0.008
					49232	221.00	222.00	1.00	0.02	-	0.40	0.074
EOH												
core stored at Matachewan												
Downhole Tests												
DDH ID	Depth	AZ	DIP									
AT-08-001	51	275.6	-48.7									
AT-08-001	102	269	-47.5									
AT-08-001	150	268.9	-47.2									
AT-08-001	201	270.7	-46.4									
AT-08-001	222	269.7	-46.3									

Opawica Explorations Inc.

Atikwa Property UTM GRID LOCATION: Atikwa Lake Area, Ontario
 DDH#: AT-08-002 452920.01 E DRILL COMPANY: DOWNING
 Az 90.00 5474663.9 N GRID: Local, Metric
 DIP -45.00 ZONE 15 E 2255.00
 E.O.H: 201 m NAD 83 N 1200.00
 Elev.: 387.28 Start: January 18, 2008; End: January 23, 2008

DDH#: AT-08-002
 Drill Company: Claim: K15375
 Downing: NQ Core
 Logged by: FRED SHARPLEY

Fred Sharpley

From	To (m)	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %	
0.00	4.20	OVBD		casing left in hole								
4.20	9.00	MF-Bx		Mafic Flow: dark green, very fine grained, weakly foliated at 70 CA; brecciated, flow; traces po								
9.00	14.24	MF		Mafic Flow: as above, amygdaloidal								
14.24	15.36	FP		Feldspar Porphyry: light grey, fine grained groundmass with fine grained white phenocrysts; contacts at 70 CA								
15.36	23.70	MF		Mafic Flow: massive; as above; traces pyrrhotite								
23.70	28.26	FP		as above: fine grained groundmass with medium grained white phenocrysts; contact at 60 CA								
28.26	38.30	MF		as above: dark green, massive								
38.30	42.94	FP		as above: coarse grained white feldspar phenocrysts in a fine grained groundmass; contacts at 70 CA	49233	42.00	42.94	0.94	0.005	-	0.012	
					49234	42.94	44.00	1.06	0.14	-	0.079	
					49235	44.00	45.00	1.00	0.24	0.24	0.041	
42.94	49.50	MF-BX		as above: flow breccia; traces pyrrhotite	49236	45.00	46.00	1.00	0.04	-	0.021	
					49237	46.00	47.00	1.00	0.02	-	0.008	
49.50	54.10	FP		as above	49238	47.00	48.00	1.00	0.22	-	0.032	
					49239	48.00	49.00	1.00	0.05	-	0.02	
54.10	56.10	MF		as above: massive	49240	49.00	49.50	0.50	0.20	-	0.067	
					49241	49.50	50.00	0.50	0.005	-	0.01	
56.10	58.90	FP		as above:	49242	Standard	53PB		0.60	-	0.55	

From	To (m)	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %	
58.90	65.60	MF		as above: massive	49243	91.00	92.00	1.00	0.08	-	0.076	
65.60	66.80	FP		as above	49244	131.00	132.00	1.00	0.02	-	0.031	
					49245	132.00	133.00	1.00	0.05	-	0.047	
66.80	68.40	MF		as above: massive	49246	142.00	143.00	1.00	0.005	-	0.018	
68.40	73.60	MF-Bx		as above: flow breccia; traces po	49247	143.00	144.00	1.00	0.10	-	0.058	
					49248	144.00	145.00	1.00	0.01	-	0.026	
73.60	74.08	FP		as above:	49249	Standard	SE29		0.57	-	0.001	
74.08	76.80	MF-Bx		as above: traces po	49250	149.57	150.00	0.43	0.55	0.62	0.139	
					49251	150.00	151.00	1.00	0.005	-	0.121	
76.80	81.30	MF		as above	49252	157.05	158.00	0.95	0.04	-	0.087	
81.30	85.90	FP		as above:	49253	158.00	159.00	1.00	0.08	-	0.065	
					49254	159.00	160.00	1.00	0.09	-	0.033	
85.90	92.80	MF-Bx		as above: traces po	49255	160.00	161.00	1.00	0.21	-	0.053	
					49256	Dup			0.08	-	0.054	
92.80	95.60	FP		as above: c.g. Pink feldspar	49257	Blank			0.005	-	0.001	
					49258	161.00	161.90	0.90	0.14	-	0.041	
95.60	96.70	MF		as above:	49259	161.90	163.00	1.10	0.02	-	0.012	
					49260	163.00	164.10	1.10	0.01	-	0.01	
96.70	98.30	FP		as above: c.g. , pink feldspar	49261	164.10	165.00	0.90	0.01	-	0.014	
					49262	165.00	166.00	1.00	0.01	0.005	0.008	
98.30	99.06	MF		as above: massive	49263	166.00	167.00	1.00	0.01	-	0.024	
					49264	167.00	168.00	1.00	0.01	-	0.021	
99.06	100.80	FP		as above: fine grained:	49265	168.00	169.00	1.00	0.005	-	0.025	
100.80	121.80	MF		as above: massive: numerous FP dikes < 1cm								
121.80	126.60	FP		as above: coarse grained:								
126.60	148.55	MF		as above: massive: medium grained								
				131.25 trace po-cpy								
				132.1 3 cm qcv at 20 CA : traces po								
				142.00-145.0 traces po								
148.55	149.57	FP		as above								
149.57	154.10	MF		as above: massive, medium grained, traces po								
154.10	157.05	FP		as above:								
157.05	161.90	MF		as above: medium grained, brecciated; tr. Po								

From	To (m)	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %	
161.90	164.10	FZ		Fault Zone: strongly sheared at 40 CA; traces po								
164.10	169.00	MF		as above: medium grained massive; quartz veining, minor pyrrhotite								
169.00	185.80	MF		as above: medium to coarse grained, massive								
185.80	186.35	FP		as above: fine grained, contact at 70 CA								
186.35	193.70	MF		as above: medium to coarse grained, massive								
193.70	194.16	FP		as above:								
194.16	201.00	MF		as above:								
				EOH								
				core stored at Matachewan								
Downhole Tests												
	DDH ID	Depth	AZ	DIP								
	AT-08-002	18	96.5	-45.6								
	AT-08-002	51	94.5	-45.8								
	AT-08-002	102	97.4	-46.2								
	AT-08-002	150	101.7	-45.3								
	AT-08-002	201	101.2	-43.8								

Opawica Explorations Inc.

Atikwa Property UTM GRID LOCATION: Atikwa Lake Area, Ontario
 DDH#: AT-08-003 452905.09 E DRILL COMPANY: DOWNING
 Az 90.00 5474462.9 N GRID: Local, Metric
 DIP -45.00 ZONE 15 E 2250.00
 E.O.H: 240 m NAD 83 N 1000.00
 Elev.: 399.63 Start: January 23, 2008; End: January 25, 2008

DDH#: AT-08-003

Drill Company: Claim: K15374
 Downing: NQ Core
 Logged by: FRED SHARPLEY

Fred Sharpley

From	To (m)	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
0.00	2.40	OVBD		casing left in hole							
2.40	12.00	MF		massive spotted, very fine grained, medium grey green ; spotted with 1-2 cm angular to subrounded fragments of granite							
12.00	12.84	FP		light grey, fine grained groundmass, fine feldspar phenocrysts, massive, contact at 80 CA							
12.84	26.90	MF		as above: massive spotted							
				15.5-17.0 blebs of pyrrhotite with quartz carbonate veining							
26.90	28.90	FP		as above:							
28.90	30.00	MF		massive spotted							
30.00	37.50	FP		as above: weakly foliated at 80 CA							
37.50	56.30	MF		as above: massive, spotted							
56.30	63.70	FP		buff to pinkish, fine grained groundmass, medium grained phenocrysts, contact at 80 CA	49266	15.00	16.00	1.00	0.23	-	0.033
					49267	16.00	17.00	1.00	0.40	-	0.097
63.70	76.30	MF		as above: non-spotted	49268	78.50	79.00	0.50	0.24	-	0.009
					49269	Standard	53PB		0.61	-	0.52
76.30	77.20	MF-Bx		Mafic Flow Breccia: dark green matrix with light grey fragments; 2-3% disseminated pyrrhotite; foliated at 70 CA	49270	79.00	80.00	1.00	0.58	0.49	0.018
					49271	80.00	81.00	1.00	0.18	-	0.008
					49272	81.00	82.00	1.00	0.37	-	0.014

From	To (m)	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
77.20	78.50	Dacite		light grey fine grained massive, unoform	49273	82.00	83.00	1.00	0.29	-	0.01
					49274	83.00	84.00	1.00	0.28	-	0.009
					49275	84.00	85.00	1.00	0.53	-	0.011
78.50	97.80	MF-Bx		as above: 3-5% disseminated pyrrhotite	49276	85.00	86.00	1.00	0.17	-	0.01
					49277	86.00	87.00	1.00	1.49	-	0.022
					49278	Dup			1.77	-	0.025
					49279	Blank			0.01	-	0.001
					49280	87.00	88.00	1.00	0.09	-	0.019
					49281	88.00	88.50	0.50	0.26	-	0.024
					49282	88.50	89.30	0.80	0.09	-	0.016
					49283	89.30	90.00	0.70	0.005	-	0.01
					49284	90.00	91.00	1.00	0.04	-	0.07
					49285	91.00	91.45	0.45	4.83	5.93	0.017
					49286	91.45	92.00	0.55	0.01	-	0.012
					49287	92.00	93.00	1.00	0.02	-	0.021
					49288	93.00	94.00	1.00	0.05	-	0.015
					49289	Standard	54Pa		2.83	-	1.46
					49290	94.00	95.00	1.00	0.97	0.97	0.013
					49291	95.00	96.00	1.00	0.37	-	0.011
					49292	96.00	97.00	1.00	0.04	-	0.022
					49293	97.00	97.80	0.80	0.05	-	0.028
					49294	110.00	110.50	0.50	0.21	-	0.009
					49295	110.50	111.20	0.70	0.29	-	0.009
					49296	111.20	112.00	0.80	0.03	-	0.003
					49297	112.00	113.00	1.00	1.09	0.95	0.015
97.80	107.40	FP		similar to 56.3-63.7	49298	113.00	113.70	0.70	0.76	-	0.011
					49299	113.70	114.50	0.80	0.83	-	0.017
107.40	108.40	MF		as above: massive	49300	114.50	114.90	0.40	0.01	-	0.011
					49301	Standard	SE29		0.58	-	0.001
108.40	108.95	FP		as above: fine grained	49302	114.90	115.30	0.40	0.05	-	0.005
					49303	115.30	116.00	0.70	0.005	-	0.011
108.95	111.20	MF		as above: massive							
111.20	111.96	FP		as above:	49304	131.00	132.00	1.00	0.77	0.83	0.062
111.96	113.70	MF-Bx		as above: mafic flow breccia; 2-3% diss. Po	49305	Dup			0.23	0.34	0.066
					49306	Blank			0.005	-	0.002
113.70	115.30	FZ		Fault Zone: light grey, strongly sheared at 70 CA; 25% quartz veining	49307	132.00	133.00	1.00	0.34	-	0.095
					49308	133.00	134.00	1.00	0.01	-	0.009
					49309	134.00	135.00	1.00	0.67	0.52	0.123
					49310	135.00	136.00	1.00	0.01	-	0.003

From	To (m)	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
					49311	136.00	137.00	1.00	0.09	-	0.024
					49312	137.00	137.50	0.50	0.15	-	0.025
					49313	137.50	138.15	0.65	0.03	-	0.025
115.30	117.80	MF		as above: massive	49314	138.15	139.00	0.85	0.07	-	0.015
					49315	139.00	140.00	1.00	0.04	-	0.015
117.80	118.25	FP		as above: fine grained	49316	Standard	53Pb		0.65	-	0.54
					49317	140.00	140.95	0.95	0.02	-	0.013
118.25	131.00	MF		as above: dark green, fine grained	49318	140.95	142.00	1.05	0.005	-	0.005
				131.0-134.0 bleached, carbonatized, moderately sheared at 133.0 at 80 CA; 1% disseminated pyrite; 2m moderately sheared							
131.00	138.15	FZ			49319	152.50	153.26	0.76	0.005	-	0.003
					49320	153.26	154.00	0.74	0.005	-	0.008
					49321	154.00	155.00	1.00	0.38	0.59	0.014
					49322	155.00	156.00	1.00	0.22	-	0.015
					49323	156.00	156.50	0.50	0.20	-	0.021
					49324	Standard	54Pa		2.88	-	1.48
					49325	156.50	158.26	1.76	0.59	0.45	0.038
					49326	158.26	159.00	0.74	0.65	-	0.034
					49327	159.00	159.80	0.80	0.04	-	0.012
					49328	159.80	160.50	0.70	0.20	-	0.039
138.15	140.95	MF-Bx		as above: flow breccia: 1-3% po	49329	160.50	161.00	0.50	0.12	-	0.037
					49330	161.00	162.00	1.00	0.005	-	0.02
					49331	162.00	163.10	1.10	0.02	-	0.012
140.95	143.20	FP		as above: fine grained	49332	173.00	174.00	1.00	0.02	-	0.007
					49333	174.00	175.20	1.20	0.16	-	0.074
143.20	148.70	MF		as above: mafic, massive	49334	175.20	176.00	0.80	1.29	-	0.155
					49335	176.00	176.65	0.65	0.01	-	0.016
148.70	149.95	FP		as above: fine grained, porphyritic	49336	176.65	177.50	0.85	0.18	-	0.144
					49337	177.50	178.00	0.50	0.56	-	0.041
149.95	153.26	MF		as above: mafic massive	49338	178.00	179.00	1.00	0.09	-	0.066
					49339	179.00	179.70	0.70	0.56	0.51	0.125
					49340	Standard	SE29		0.63	-	0.001
					49341	179.70	180.50	0.80	0.07	-	0.014
					49342	191.00	192.00	1.00	0.03	-	0.031
153.26	158.26	MF-BX		as above: brecciated, 1-3% po	49343	197.00	198.00	1.00	0.04	-	0.046

From	To (m)	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
158.26	159.80	FP		as above: fine grained							
159.80	163.10	MF-Bx		brecciated: 1-3% po							
163.10	171.30	FP		as above: fine grained; contact at 40 CA							
171.30	174.00	MF		massive							
174.00	175.20	MF-Bx		1-3% po							
175.20	176.65	FP		as above:							
176.65	179.70	MF-Bx		1-3% po							
179.70	183.95	MF		as above:							
183.95	185.25	FP		as above: coarse white phenocrysts							
185.25	207.40	MF		as above: massive:							
207.40	207.90	FP		as above: medium grained phenocrysts							
207.90	233.20	MF		as above: massive:							
233.20	240.00	FP		as above: coarse phenocrysts							
				EOH							
				core stored at Matachewan							
Downhole Tests											

From	To (m)	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
DDH ID	Depth	AZ	DIP								
AT-08-003	18	90.4	-44.3								
AT-08-003	51	91.8	-44.5								
AT-08-003	102	90.1	-44.6								
AT-08-003	150	97	-43.5								
AT-08-003	201	100.8	-42.3								
AT-08-003	240	102.4	-41.2								

Opawica Explorations Inc.

Atikwa Property UTM GRID LOCATION: Atikwa Lake Area, Ontario
 DDH#: AT-08-004 452904.4 E DRILL COMPANY: DOWNING
 Az 270.00 5474462.9 N GRID: Local, Metric
 DIP -45.00 ZONE 15 E 2250.00
 E.O.H: 398.6 m NAD 83 N 1000.00
 Elev.: 399.65 Start: January 26, 2008; End: January 31, 2008

DDH#: AT-08-004
 Drill Company: Claim: K15374
 Downing: NQ Core
 Logged by: FRED SHARPLEY

Fred Sharpley

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	AU2 g/t	Cu %
0.00	3.40	OVBD		casing left in hole							
3.40	11.00	MF		Mafic Flow: spotted, medium grey, massive, uniform, very fine grained;							
11.00	50.90	PF		spotted, scattered pillows							
					49344	16.00	17.00	1.00	0.005		0.055
					49345	17.00	18.00	1.00	0.19	0.20	0.12
					49346	18.00	19.00	1.00	0.02		0.028
					49347	19.00	20.00	1.00	0.01		0.006
					49348	20.00	21.00	1.00	0.02		0.008
					49349	21.00	22.00	1.00	0.005		0.003
					49350	22.00	23.00	1.00	0.005		0.004
					49351	23.00	24.00	1.00	0.01		0.024
					49352	24.00	25.00	1.00	0.01		0.018
					49353	Standard	53Pb		0.62		0.54
					49354	25.00	26.00	1.00	0.02		0.002
					49355	26.00	27.00	1.00	0.005		0.009
					49356	27.00	28.00	1.00	0.005		0.003
					49357	28.00	29.00	1.00	0.01		0.028
					49358	29.00	30.00	1.00	0.01		0.006
					49359	30.00	31.00	1.00	0.09		0.093

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	AU2 g/t	Cu %
					49360	31.00	32.00	1.00	0.03		0.033
					49361	32.00	33.00	1.00	0.07	0.05	0.026
					49362	Dup			0.07		0.029
					49363	Blank			0.01		0.001
					49364	33.00	34.00	1.00	0.09		0.011
					49365	34.00	35.00	1.00	0.01		0.006
					49366	35.00	36.00	1.00	0.04		0.112
					49367	36.00	37.00	1.00	0.01		0.009
					49368	37.00	38.00	1.00	0.02		0.034
					49369	38.00	39.00	1.00	0.04		0.047
					49370	39.00	40.00	1.00	0.05	0.05	0.074
					49371	40.00	41.00	1.00	0.02		0.007
					49372	41.00	42.00	1.00	0.04		0.005
					49373	Standard	54Pa		2.86		1.48
					49374	42.00	43.00	1.00	0.02		0.002
					49375	43.00	44.00	1.00	0.01		0.007
					49376	44.00	45.00	1.00	0.02		0.003
					49377	45.00	46.00	1.00	0.02		0.019
					49378	46.00	47.00	1.00	0.01		0.005
					49379	47.00	48.00	1.00	0.02		0.009
					49380	48.00	49.00	1.00	0.02	0.01	0.001
					49381	49.00	50.00	1.00	0.02		0.004
					49382	Dup			0.02		0.001
					49383	Blank			0.005		0.002
					49384	50.00	50.90	0.90	0.02		0.016
50.90	70.40	FP		light grey, coarse grained phenocrysts in a medium to fine grained matrix, massive uniform							
					49385	70.40	71.00	0.60	0.02		0.008
70.40	108.00	PF		as above: spotted; weak pillow flow, scattered	49386	71.00	72.00	1.00	0.02		0.012
					49387	72.00	73.00	1.00	0.01		0.008
					49388	73.00	74.00	1.00	0.01		0.018
					49389	74.00	75.00	1.00	0.005		0.003
					49390	75.00	76.00	1.00	0.02	0.03	0.009
					49391	76.00	77.00	1.00	0.02		0.026
					49392	Standard	SE29		0.60		0.001
					49393	77.00	78.00	1.00	0.01		0.004
					49394	78.00	79.00	1.00	0.04		0.002
					49395	79.00	80.00	1.00	0.01		0.01
					49396	80.00	81.00	1.00	0.02		0.016
					49397	81.00	82.00	1.00	0.03		0.03
					49398	82.00	83.00	1.00	0.05		0.067
					49399	83.00	84.00	1.00	0.35	0.30	0.056
					49400	84.00	85.00	1.00	0.04		0.037

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	AU2 g/t	Cu %
					49401	Dup			0.03		0.039
					49402	Blank			0.005		0.001
					49403	85.00	86.00	1.00	0.06		0.165
					49404	86.00	87.00	1.00	0.15	-	0.261
					49405	87.00	88.00	1.00	0.03	-	0.042
					49406	88.00	89.00	1.00	0.005	-	0.056
					49407	89.00	90.00	1.00	0.05	-	0.079
					49408	90.00	91.00	1.00	0.04	-	0.055
					49409	91.00	92.00	1.00	0.04	-	0.05
					49410	92.00	93.00	1.00	0.12	0.13	0.271
					49411	93.00	94.00	1.00	0.01	-	0.016
					49412	Standard	53Pb		0.62	-	0.54
					49413	94.00	95.00	1.00	0.01	-	0.013
					49414	95.00	96.00	1.00	0.01	-	0.018
					49415	96.00	97.00	1.00	0.005	-	0.001
					49416	97.00	98.00	1.00	0.03	-	0.043
					49417	98.00	99.00	1.00	0.005	-	0.04
					49418	99.00	100.00	1.00	0.09	-	0.02
					49419	100.00	101.00	1.00	0.18	-	0.62
					49420	101.00	102.00	1.00	0.13	0.13	0.177
					49421	Dup			0.12	-	0.168
					49422	Blank			0.005	-	0.002
					49423	102.00	103.00	1.00	0.21	-	0.325
					49424	103.00	104.00	1.00	0.26	0.23	0.264
					49425	104.00	105.00	1.00	0.06	-	0.085
					49426	105.00	106.00	1.00	0.06	-	0.08
					49427	106.00	107.00	1.00	0.10	0.13	0.086
					49428	107.00	108.00	1.00	0.005	-	0.004
					49429	108.00	109.00	1.00	0.01	-	0.008
108.00	138.00	MF		as above: massive, non-spotted, vesicular	49430	109.00	110.00	1.00	0.005	-	0.004
					49431	110.00	111.00	1.00	0.01	-	0.01
					49432	Standard	54Pa		2.78	-	1.49
				128.0-129.5 vesicles filled with pyrrhotite	49433	111.00	112.00	1.00	0.005	-	0.011
					49434	112.00	113.00	1.00	0.01	-	0.01
					49435	113.00	114.00	1.00	0.005	-	0.001
					49436	114.00	115.00	1.00	0.005	-	0.001
					49437	115.00	116.00	1.00	0.01	-	0.008
					49438	116.00	117.00	1.00	0.005	0.01	0.001
					49439	117.00	118.00	1.00	0.005	-	0.001
					49440	118.00	119.00	1.00	0.005	-	0.001
					49441	Dup			0.005	-	0.002
					49442	Blank			0.005	-	0.001
					49443	119.00	120.00	1.00	0.005	-	0.001

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	AU2 g/t	Cu %
					49444	120.00	121.00	1.00	0.005	-	0.001
					49445	121.00	122.00	1.00	0.01	-	0.001
					49446	122.00	123.00	1.00	0.01	0.005	0.001
					49447	123.00	124.00	1.00	0.005	-	0.001
					49448	124.00	125.00	1.00	0.005	-	0.001
					49449	125.00	126.00	1.00	0.005	-	0.001
					49450	126.00	127.00	1.00	0.005	-	0.001
					49451	127.00	128.00	1.00	0.01	-	0.003
					49452	Standard	SE29		0.58	-	0.001
					49453	128.00	129.00	1.00	0.01	-	0.011
					49454	129.00	130.00	1.00	0.005	-	0.006
					49455	130.00	131.00	1.00	0.005	-	0.004
					49456	131.00	132.00	1.00	0.01	-	0.004
					49457	132.00	133.00	1.00	0.005	0.005	0.001
					49458	133.00	134.00	1.00	0.01	-	0.001
					49459	134.00	135.00	1.00	0.005	-	0.001
					49460	135.00	136.00	1.00	0.005	-	0.001
					49461	Dup			0.01	-	0.001
					49462	Blank			0.005	-	0.001
					49463	136.00	137.00	1.00	0.005	-	0.001
138.00	189.66	MF		as above: massive, spotted, vesicular	49464	137.00	138.00	1.00	0.005		0.002
					49465	138.00	139.00	1.00	0.005		0.001
					49466	139.00	140.00	1.00	0.005		0.005
					49467	140.00	141.00	1.00	0.005		0.008
					49468	141.00	142.00	1.00	0.005		0.005
					49469	142.00	143.00	1.00	0.005	0.01	0.005
					49470	143.00	144.00	1.00	0.005		0.009
					49471	144.00	145.00	1.00	0.005		0.009
					49472	Standard	53Pb		0.57		0.55
					49473	145.00	146.00	1.00	0.005		0.005
					49474	146.00	147.00	1.00	0.005		0.006
					49475	147.00	148.00	1.00	0.005		0.007
					49476	148.00	149.00	1.00	0.005		0.01
					49477	149.00	150.00	1.00	0.005		0.007
					49478	150.00	151.00	1.00	0.005		0.008
					49479	151.00	152.00	1.00	0.005		0.018
					49480	152.00	153.00	1.00	0.03		0.034
					49481	Dup			0.02	0.04	0.035
					49482	Blank			0.005		0.002
					49483	153.00	154.00	1.00	0.04		0.029
					49484	154.00	155.00	1.00	0.005		0.008
					49485	155.00	156.00	1.00	0.005		0.003
					49486	156.00	157.00	1.00	0.03		0.029

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	AU2 g/t	Cu %
					49487	157.00	158.00	1.00	0.03		0.027
					49488	158.00	159.00	1.00	0.04		0.04
					49489	159.00	160.00	1.00	0.005		0.028
					49490	160.00	161.00	1.00	0.005		0.028
					49491	161.00	162.00	1.00	0.01		0.007
					49492	Standard	54Pa		2.85		1.49
					49493	162.00	163.00	1.00	0.01	0.005	0.002
					49494	163.00	164.00	1.00	0.005		0.009
					49495	164.00	165.00	1.00	0.01		0.012
					49496	165.00	166.00	1.00	0.02	0.01	0.009
					49497	166.00	167.00	1.00	0.005		0.01
					49498	167.00	168.00	1.00	0.005		0.008
					49499	168.00	169.00	1.00	0.01		0.01
					49500	169.00	170.00	1.00	0.005		0.002
					49501	Dup			0.005		0.002
					49502	Blank			0.005		0.001
					49503	170.00	171.00	1.00	0.005		0.004
					49504	171.00	172.00	1.00	0.01		0.008
					49505	172.00	173.00	1.00	0.03		0.022
					49506	173.00	174.00	1.00	0.005		0.006
					49507	174.00	175.00	1.00	0.02		0.027
					49508	175.00	176.00	1.00	0.005		0.002
					49509	176.00	177.00	1.00	0.005		0.022
					49510	177.00	178.00	1.00	0.01	0.005	0.016
					49511	178.00	179.00	1.00	0.005		0.039
					49512	Standard	52Pb		0.32		0.337
					49513	179.00	180.00	1.00	0.01		0.014
					49514	180.00	181.00	1.00	0.02		0.017
					49515	181.00	182.00	1.00	0.06		0.054
					49516	182.00	183.00	1.00	0.15		0.105
					49517	183.00	184.00	1.00	0.02		0.021
					49518	184.00	185.00	1.00	0.04		0.02
					49519	185.00	186.00	1.00	0.05	0.06	0.033
					49520	186.00	187.00	1.00	0.005		0.008
					49521	Dup			0.005		0.007
					49522	Blank			0.005		0.001
					49523	187.00	188.00	1.00	0.01		0.008
					49524	188.00	189.00	1.00	0.005		0.001
					49525	189.00	189.66	0.66	0.005		0.001
189.66	193.10	FP		as above: contact at 40 CA	49526	189.66	190.00	0.34	0.005		0.014
					49527	190.00	191.00	1.00	0.005		0.01
				190.23-191.2 MF	49528	191.00	192.00	1.00	0.11		0.141
					49529	192.00	193.10	1.10	0.10	0.10	0.099

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	AU2 g/t	Cu %
193.10	200.00	MF		as above:	49530	193.10	194.00	0.90	0.02		0.016
					49531	194.00	195.00	1.00	0.01		0.006
					49532	Standard	53Pb		0.61		0.55
					49533	195.00	196.00	1.00	0.02		0.012
					49534	196.00	197.00	1.00	0.005		0.005
					49535	197.00	198.00	1.00	0.02		0.015
					49536	198.00	199.00	1.00	0.005		0.008
					49537	199.00	200.00	1.00	0.04		0.045
200.00	220.00	MF		medium to dark green, massive, non-spotted	49538	200.00	201.00	1.00	0.35		0.315
					49539	201.00	202.00	1.00	0.65	0.39	0.68
				200-206.5 weakly bleached, sheared at 10 CA	49540	202.00	203.00	1.00	0.20		0.084
					49541	Dup			0.37		0.073
					49542	Blank			0.01		0.003
					49543	203.00	204.00	1.00	0.005		0.008
					49544	204.00	205.00	1.00	0.005		0.002
					49545	205.00	206.00	1.00	0.005		0.004
					49546	206.00	207.00	1.00	0.005		0.01
					49547	207.00	208.00	1.00	0.005		0.001
					49548	208.00	209.00	1.00	0.13	0.16	0.078
					49549	209.00	210.00	1.00	0.01		0.002
					49550	210.00	211.00	1.00	0.005		0.001
					49551	211.00	212.00	1.00	0.005		0.001
					49552	Standard	54Pa		2.81		1.49
					49553	212.00	213.00	1.00	0.005		0.006
					49554	213.00	214.00	1.00	0.02		0.004
					49555	214.00	215.00	1.00	0.005		0.003
					49556	215.00	216.00	1.00	0.005		0.006
					49557	216.00	217.00	1.00	0.01		0.006
					49558	217.00	218.00	1.00	0.005		0.006
					49559	218.00	219.00	1.00	0.01	0.005	0.005
					49560	219.00	220.00	1.00	0.01		0.005
					49561	Dup			0.01		0.005
					49562	Blank			0.01		0.001
220.00	222.00	FZ		light to medium grey, very fine grained, moderately sheared at 10-20 CA; bleached, silicified	49563	220.00	221.00	1.00	0.01		0.004
					49564	221.00	222.00	1.00	0.01		0.001
222.00	235.00	MF		light to medium grey, very fine grained, bleached, silicified	49565	222.00	223.00	1.00	0.01		0.001
					49566	223.00	224.00	1.00	0.01		0.001
					49567	224.00	225.00	1.00	0.02		0.004
					49568	225.00	226.00	1.00	0.01		0.012
					49569	226.00	227.00	1.00	0.01		0.002

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	AU2 g/t	Cu %
					49570	227.00	228.00	1.00	0.13		0.004
					49571	228.00	229.00	1.00	0.01		0.002
					49572	Standard	52Pb		0.32		0.336
					49573	229.00	230.00	1.00	0.01		0.001
					49574	230.00	231.00	1.00	0.005		0.001
					49575	231.00	232.00	1.00	0.01		0.001
					49576	232.00	233.00	1.00	0.01		0.001
					49577	233.00	234.00	1.00	0.005		0.001
					49578	234.00	235.00	1.00	0.005		0.001
235.00	238.00	FZ		similar to above: sheared at 10-20 CA	49579	235.00	236.00	1.00	0.01	0.02	0.002
					49580	236.00	237.00	1.00	0.005		0.001
					49581	Dup			0.005		0.001
					49582	Blank			0.005		0.007
					49583	237.00	238.00	1.00	0.005		0.001
238.00	269.00	MF		light to medium grey, very fine grained, massive, moderately silicified, traces of pyrite	49584	238.00	239.00	1.00	0.01		0.001
					49585	239.00	240.00	1.00	0.01		0.001
					49586	240.00	241.00	1.00	0.005		0.001
					49587	241.00	242.00	1.00	0.02		0.003
					49588	242.00	243.00	1.00	0.07		0.012
					49589	243.00	244.00	1.00	0.02		0.005
					49590	244.00	245.00	1.00	0.005		0.001
					49591	245.00	246.00	1.00	0.01		0.001
					49592	Standard	53Pb		0.61		0.55
					49593	246.00	247.00	1.00	0.01		0.001
					49594	247.00	248.00	1.00	0.005		0.001
					49595	248.00	249.00	1.00	0.005	0.005	0.001
					49596	249.00	250.00	1.00	0.005		0.001
					49597	250.00	251.00	1.00	0.005		0.001
					49598	251.00	252.00	1.00	0.01		0.003
					49599	252.00	253.00	1.00	0.01		0.001
					49600	253.00	254.00	1.00	0.01		0.001
					49601	Dup			0.005		0.001
					49602	Blank			0.005		0.001
					49603	254.00	255.00	1.00	0.005		0.001
					49604	255.00	256.00	1.00	0.005	0.01	0.001
					49605	256.00	257.00	1.00	0.005		0.001
					49606	257.00	258.00	1.00	0.01		0.001
					49607	258.00	259.00	1.00	0.005		0.002
					49608	259.00	260.00	1.00	0.01		0.014
					49609	260.00	261.00	1.00	0.02		0.041
					49610	261.00	262.00	1.00	0.03		0.051
					49611	262.00	263.00	1.00	0.14	0.15	0.239

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	AU2 g/t	Cu %
					49612	Standard	54Pa		2.85		1.49
					49613	263.00	264.00	1.00	0.09		0.174
					49614	264.00	265.00	1.00	0.09		0.002
					49615	265.00	266.00	1.00	0.04		0.065
					49616	266.00	267.00	1.00	0.07		0.013
					49617	267.00	268.00	1.00	2.61	1.71	0.008
					49618	268.00	269.00	1.00	0.03		0.002
269.00	273.00	FZ		light to medium grey, very fine grained, moderately sheared at 10-20 CA; bleached, silicified	49619	269.00	270.00	1.00	0.23		0.014
					49620	270.00	271.00	1.00	0.02		0.007
					49621	Dup			0.02		0.008
					49622	Blank			0.005		0.001
					49623	271.00	272.00	1.00	0.02		0.016
					49624	272.00	273.00	1.00	0.01		0.019
273.00	280.00	MF		light to medium grey, very fine grained, massive, moderately silicified, traces of pyrite	49625	273.00	274.00	1.00	0.005		0.005
					49626	274.00	275.00	1.00	0.04		0.066
					49627	275.00	276.00	1.00	0.01		0.009
					49628	276.00	277.00	1.00	0.62	0.24	0.008
					49629	277.00	278.00	1.00	0.10		0.004
					49630	278.00	279.00	1.00	0.005		0.002
					49631	279.00	280.00	1.00	0.005		0.002
					49632	Standard	52Pb		0.32		0.336
280.00	283.00	FZ		light to medium grey, very fine grained, moderately sheared at 10-20 CA; bleached, silicified	49633	280.00	281.00	1.00	0.02	0.02	0.004
					49634	281.00	282.00	1.00	0.02		0.012
					49635	282.00	283.00	1.00	0.06		0.063
283.00	286.00	MF		light to medium grey, very fine grained, massive, moderately silicified, traces of pyrite; possible porphyry	49636	283.00	284.00	1.00	0.07		0.034
					49637	284.00	285.00	1.00	0.08		0.028
					49638	285.00	286.00	1.00	0.07		0.039
286.00	289.70	FZ		light to medium grey, very fine grained, moderately sheared at 10-20 CA; bleached, silicified	49639	286.00	287.00	1.00	0.48		0.116
					49640	287.00	288.00	1.00	0.31		0.137
289.70	292.00	MF		light to medium grey, very fine grained, massive, moderately silicified, traces of pyrite; hornblende phenocrysts <2mm; sharp contact at 30 CA	49641	Dup			0.24		0.133
					49642	Blank			0.01		0.002
					49643	288.00	289.00	1.00	0.14		0.136

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
					49644	289.00	289.70	0.70	0.02		0.014
292.00	305.00	MF		light to medium grey, very fine grained, massive, moderately silicified, 1-3% disseminated chalcopyrite, pyrite in vesicles; foliated at 20 CA; possible porphyry	49645	289.70	290.00	0.30	0.09		0.061
					49646	290.00	291.00	1.00	0.12		0.074
					49647	291.00	292.00	1.00	0.08		0.041
					49648	292.00	293.00	1.00	0.47		0.329
					49649	293.00	294.00	1.00	0.52	0.60	0.315
					49650	294.00	295.00	1.00	0.05		0.032
					49651	295.00	296.00	1.00	0.23		0.234
					49652	Standard	53Pb		0.62		0.54
					49653	296.00	297.00	1.00	0.15		0.223
					49654	297.00	298.00	1.00	0.25		0.221
					49655	298.00	299.00	1.00	0.16		0.253
					49656	299.00	300.00	1.00	0.09		0.174
					49657	300.00	301.00	1.00	0.09		0.162
					49658	301.00	302.00	1.00	0.16		0.098
					49659	302.00	303.00	1.00	0.13		0.216
					49660	303.00	304.00	1.00	0.13	0.08	0.168
					49661	Dup			0.10		0.166
					49662	Blank			0.01		0.001
					49663	304.00	305.00	1.00	0.98		0.446
305.00	308.00	FZ		light to medium grey, very fine grained, moderately sheared at 10-20 CA; bleached, silicified	49664	305.00	306.00	1.00	0.08		0.067
					49665	306.00	307.00	1.00	0.11		0.084
					49666	307.00	308.00	1.00	0.10		0.113
308.00	313.00	MF		light to medium grey, very fine grained, massive, moderately silicified, 1-3% disseminated chalcopyrite, pyrite in vesicles; foliated at 20 CA; possible porphyry	49667	308.00	309.00	1.00	0.12		0.226
					49668	309.00	310.00	1.00	0.11		0.195
					49669	310.00	311.00	1.00	0.30		0.187
					49670	311.00	312.00	1.00	0.12	0.13	0.132
					49671	312.00	313.00	1.00	0.13		0.157
					49672	Standard	54Pa		2.85		1.49
313.00	371.45	FP		light to medium grey, coarse grained white phenocrysts in a fine grained groundmass; minor pyrite; weak sericite alteration, minor muscovite; weakly foliated; contact at 20 CA	49673	313.00	314.00	1.00	0.19		0.196
					49674	314.00	315.00	1.00	0.06		0.083
					49675	315.00	316.00	1.00	0.005		0.051

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	AU2 g/t	Cu %
					49676	316.00	317.00	1.00	0.005		0.023
					49677	317.00	318.00	1.00	0.005		0.034
					49678	318.00	319.00	1.00	0.15	0.16	0.022
					49679	319.00	320.00	1.00	0.005		0.011
					49680	320.00	321.00	1.00	0.01		0.019
					49681	Dup			0.01		0.021
					49682	Blank			0.005		0.001
					49683	321.00	322.00	1.00	0.005		0.026
					49684	322.00	323.00	1.00	0.02		0.023
					49685	323.00	324.00	1.00	0.005		0.034
					49686	324.00	325.00	1.00	0.03	0.03	0.043
					49687	325.00	326.00	1.00	0.03		0.039
					49688	326.00	327.00	1.00	0.12		0.043
					49689	327.00	328.00	1.00	0.005		0.018
					49690	328.00	329.00	1.00	0.02		0.021
					49691	329.00	330.00	1.00	0.005		0.018
					49692	Standard	52Pb		0.32		0.335
					49693	330.00	331.00	1.00	0.005		0.006
					49694	331.00	332.00	1.00	0.03		0.031
					49695	332.00	333.00	1.00	0.06		0.094
					49696	333.00	334.00	1.00	0.08		0.093
					49697	334.00	335.00	1.00	0.08	0.07	0.087
					49698	335.00	336.00	1.00	0.12		0.094
					49699	336.00	337.00	1.00	0.06		0.061
					49700	337.00	338.00	1.00	0.09		0.054
					49701	Dup			0.07		0.056
					49702	Blank			0.005		0.001
					49703	338.00	339.00	1.00	0.09		0.063
					49704	339.00	340.00	1.00	0.11		0.062
					49705	340.00	341.00	1.00	0.07	0.08	0.061
					49706	341.00	342.00	1.00	0.02		0.057
					49707	342.00	343.00	1.00	0.06		0.057
					49708	343.00	344.00	1.00	0.04		0.051
					49709	344.00	345.00	1.00	0.07	0.04	0.058
					49710	345.00	346.00	1.00	0.05		0.05
					49711	346.00	347.00	1.00	0.08		0.063
					49712	Standard	53Pb		0.60		0.55
					49713	347.00	348.00	1.00	0.16		0.101
					49714	348.00	349.00	1.00	0.04		0.067
					49715	349.00	350.00	1.00	0.05		0.063
					49716	350.00	351.00	1.00	0.05		0.069
					49717	351.00	352.00	1.00	0.01		0.09
					49718	352.00	353.00	1.00	0.15	0.20	0.12

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	AU2 g/t	Cu %
					49719	353.00	354.00	1.00	0.05		0.068
					49720	354.00	355.00	1.00	0.05		0.07
					49721	Dup			0.05		0.075
					49722	Blank			0.01		0.002
					49723	355.00	356.00	1.00	0.07		0.076
					49724	356.00	357.00	1.00	0.04		0.061
					49725	357.00	358.00	1.00	0.14		0.06
					49726	358.00	359.00	1.00	0.03		0.063
					49727	359.00	360.00	1.00	0.06		0.074
					49728	360.00	361.00	1.00	0.05		0.085
					49729	361.00	362.00	1.00	0.09		0.105
					49730	362.00	363.00	1.00	0.10		0.076
					49731	363.00	364.00	1.00	0.07		0.086
					49732	Standard	54Pa		2.89		1.48
					49733	364.00	365.00	1.00	0.40	0.48	0.195
					49734	365.00	366.00	1.00	0.03		0.061
					49735	366.00	367.00	1.00	0.07		0.069
					49736	367.00	368.00	1.00	0.16		0.13
					49737	368.00	369.00	1.00	0.15		0.117
					49738	369.00	370.00	1.00	0.16		0.126
					49739	370.00	371.00	1.00	0.11	0.09	0.125
					49740	371.00	371.45	0.45	0.09		0.134
					49741	Dup			0.08		0.126
					49742	Blank			0.005		0.002
371.45	398.60	Dacite		Dacite: light grey, very fine grained, massive, uniform; numerous quartz carbonate veins at 50 CA	49743	371.45	372.00	0.55	0.09		0.177
					49744	372.00	373.00	1.00	0.12		0.171
					49745	373.00	374.00	1.00	0.15		0.265
					49746	374.00	375.00	1.00	0.21		0.202
					49747	375.00	376.00	1.00	0.36	0.45	0.277
					49748	376.00	377.00	1.00	0.14		0.128
					49749	377.00	378.00	1.00	0.03		0.074
					49750	378.00	379.00	1.00	1.45	1.33	0.054
					49751	379.00	380.00	1.00	0.05		0.054
					49752	Standard	52Pb		0.32		0.334
					49753	380.00	381.00	1.00	0.04		0.045
					49754	381.00	382.00	1.00	0.04	-	0.069
					49755	382.00	383.00	1.00	0.43	-	0.051
				383-384 sheared at 20 CA	49756	383.00	384.00	1.00	11.73	14.40	0.022
					49757	384.00	385.00	1.00	0.06	-	0.022
					49758	385.00	386.00	1.00	0.18	-	0.143
					49759	386.00	387.00	1.00	0.14	0.25	0.132

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	AU2 g/t	Cu %
					49760	387.00	388.00	1.00	0.35	-	0.149
					49761	Dup			0.44	-	0.151
					49762	Blank			0.01	-	0.002
					49763	388.00	389.00	1.00	0.09	-	0.156
					49764	389.00	390.00	1.00	0.24	-	0.226
					49765	390.00	391.00	1.00	0.19	-	0.195
					49766	391.00	392.00	1.00	0.32	-	0.336
					49767	392.00	393.00	1.00	0.15	-	0.165
					49768	393.00	394.00	1.00	0.34	-	0.01
					49769	394.00	395.00	1.00	0.04	-	0.014
					49770	395.00	396.00	1.00	0.08	0.08	0.01
					49771	396.00	397.00	1.00	0.07	-	0.032
					49772	Standard	53Pb		0.62	-	0.54
					49773	397.00	398.00	1.00	0.05	-	0.027
					49774	398.00	398.60	0.60	0.02	-	0.018
				EOH							
				core stored at Matachewan							
Downhole Tests											
	DDH ID	Depth	AZ	DIP							
	AT-08-004	18	268.1	-47.9							
	AT-08-004	51	267.1	-47.9							
	AT-08-004	105	267.5	-47.7							
	AT-08-004	150	267.4	-47.5							
	AT-08-004	201	267	-47.3							
	AT-08-004	255	267.3	-47.7							
	AT-08-004	300	267.8	-46.8							
	AT-08-004	351	271.2	-45.3							
	AT-08-004	402	274.3	-44							

Opawica Explorations Inc.

Atikwa Property UTM GRID LOCATION: Atikwa Lake Area, Ontario
 DDH#: AT-08-005 453144.37 E DRILL COMPANY: DOWNING
 Az 90.00 5474656.9 N GRID: Local, Metric:
 DIP -45.00 ZONE 15 E 2477.00
 E.O.H: 147 m NAD 83 N 1200.00
 Elev.: 367.81 Start: February 1, 2008; End: February 2, 2008

AT-08-005
 Drill Company: Claim: K15376
 Downing: NQ Core
 Logged by: FRED SHARPLEY

Fred Sharpley

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
0.00	1.00	OVBD		casing left in hole							
1.00	32.60	FP		pale grey, coarse grained, white phenocrysts in medium grained groundmass; contact at 20 CA							
				8.2 chalcopyrite							
				20.6 1 cm chalcopyrite, pyrite vein at 40 CA							
				21.0 15 cm qv at 60 CA; traces pyrite, chalcopyrite							
32.60	35.50	MF		greenish, massive, very fine grained							
35.50	36.50	FZ		strongly sheared at 60 CA							
36.50	42.30	MF		as above: massive, spotted							
42.30	46.80	Dio		Mafic Dike: dark green, medium grained, massive, or hornblende rich andesite; diorite							
46.80	49.85	MF		massive, spotted	49775	7.00	8.00	1.00	0.005	-	0.012
49.85	52.20	Dio		Mafic Dike:	49776	8.00	9.00	1.00	0.06	-	0.056
					49777	9.00	10.00	1.00	0.005	-	0.012
52.20	67.20	MF		massive, spotted	49778	19.00	20.00	1.00	0.09	-	0.092
67.20	84.18	Dio		Mafic Dike: 1% disseminated chalcopyrite	49779	20.00	21.00	1.00	2.37	-	0.51
					49780	21.00	22.00	1.00	4.15	4.05	0.343
				69.3-71.7 MF							
					49781	66.00	66.50	0.50	1.32	-	0.014
					49782	Standard	53Pb		0.62	-	0.54
					49783	66.50	67.20	0.70	0.005	-	0.009
					49784	67.20	68.00	0.80	0.32	-	0.249
					49785	68.00	69.00	1.00	0.50	-	0.475
					49786	69.00	70.00	1.00	0.17	-	0.191
					49787	70.00	71.00	1.00	0.02	-	0.018
					49788	71.00	72.00	1.00	0.16	-	0.152

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
					49789	72.00	73.00	1.00	0.28	-	0.219
					49790	73.00	74.00	1.00	0.18	-	0.173
					49791	Dup			0.15	-	0.161
					49792	Blank			0.01	-	0.004
					49793	74.00	75.00	1.00	0.25	0.22	0.241
					49794	75.00	76.00	1.00	0.13	-	0.196
					49795	76.00	77.00	1.00	0.16	-	0.267
					49796	77.00	78.00	1.00	0.16	-	0.17
					49797	78.00	79.00	1.00	0.07	-	0.089
					49798	79.00	80.00	1.00	0.11	-	0.108
				80.4-80.9 MF	49799	80.00	81.00	1.00	0.09	-	0.109
					49800	81.00	82.00	1.00	0.02	-	0.042
					49801	82.00	83.00	1.00	0.005	-	0.009
					49802	Standard	54Pa		2.81	-	1.49
					49803	83.00	83.50	0.50	0.005	-	0.007
84.18	85.10	FP		medium grained phenocrysts in a fine grained groundmass, massive, uniform	49804	83.50	84.18	0.68	0.01	-	0.002
					49805	84.18	85.10	0.92	0.005	-	0.003
85.10	87.80	MF		massive, fine grained	49806	85.10	86.00	0.90	0.005	-	0.004
					49807	86.00	87.00	1.00	0.005	-	0.005
					49808	87.00	87.80	0.80	0.005	-	0.004
87.80	92.40	Dio		as above: fine to medium grained, massive	49809	87.80	88.50	0.70	0.23	0.22	0.253
					49810	88.50	89.00	0.50	0.16	-	0.187
					49811	Dup			0.15	-	0.194
					49812	Blank			0.01	-	0.004
					49813	89.00	90.00	1.00	0.10	-	0.135
					49814	90.00	91.00	1.00	0.05	-	0.058
					49815	91.00	92.00	1.00	0.14	-	0.184
					49816	92.00	92.40	0.40	0.13	-	0.051
92.40	94.14	FP		as above: massive	49817	92.40	93.00	0.60	0.03	-	0.027
					49818	93.00	94.14	1.14	0.03	-	0.03
94.14	96.00	Dio		as above: fine grained	49819	94.14	95.00	0.86	0.08	-	0.055
					49820	95.00	96.00	1.00	0.08	-	0.054
96.00	96.90	FP			49821	96.00	96.90	0.90	0.10	0.11	0.088
					49822	Standard	52Pb		0.31	-	0.337
96.90	97.70	Dio		as above: fine grained	49823	96.90	97.70	0.80	0.08	-	0.069
					49824	97.70	98.70	1.00	0.02	-	0.017
97.70	98.70	MF			49825	98.70	99.50	0.80	0.04	-	0.039
					49826	99.50	100.00	0.50	0.02	-	0.075
98.70	103.10	Dio		dark green, fine grained, massive	49827	100.00	101.00	1.00	0.07	-	0.181
					49828	101.00	102.00	1.00	0.12	-	0.256
					49829	102.00	103.10	1.10	0.07	-	0.167

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
103.10	104.20	FP		pinkish, medium grained white feldspar phenocrysts in a fine grained groundmass; granite porphyry	49830	103.10	104.20	1.10	0.01	-	0.011
					49831	Dup			0.005	-	0.01
104.20	104.80	Dio		as above: contact at 70 CA	49832	Blank			0.005	-	0.005
					49833	104.20	104.80	0.60	0.07	0.10	0.322
					49834	104.80	105.80	1.00	0.01	-	0.009
104.80	117.50	FP		as above:							
117.50	118.90	Dio		as above:	49835	117.50	118.00	0.50	0.06	-	0.093
					49836	118.00	118.90	0.90	0.06	-	0.089
118.90	132.00	FP		as above:							
132.00	134.60	Dio		as above:	49837	132.00	133.00	1.00	0.01	-	0.006
					49838	Standard	53Pb		0.63	-	0.55
					49839	133.00	134.00	1.00	0.005	-	0.005
					49840	134.00	134.60	0.60	0.01	-	0.008
134.60	135.66	FP		as above:	49841	134.60	135.66	1.06	0.02	-	0.03
					49842	135.66	136.00	0.34	0.005	-	0.046
135.66	141.80	MF		massive, spotted	49843	136.00	137.00	1.00	0.005	-	0.009
					49844	137.00	138.00	1.00	0.005	-	0.009
					49845	138.00	139.00	1.00	0.03	-	0.03
					49846	139.00	140.00	1.00	0.02	-	0.011
					49847	Dup			0.03	-	0.009
					49848	Blank			0.005	-	0.002
					49849	140.00	141.00	1.00	0.03	-	0.015
141.80	142.85	FP		as above:	49850	141.00	141.80	0.80	0.01	-	0.007
					49851	141.80	142.85	1.05	0.04	-	0.017
142.85	147.00	MF		as above: massive, spotted	49852	142.85	143.50	0.65	0.10	0.10	0.069
					49853	143.50	144.00	0.50	0.005	-	0.002
					49854	144.00	145.00	1.00	0.02	-	0.001
				EOH	49855	145.00	146.00	1.00	0.08	-	0.002
					49856	146.00	147.00	1.00	0.03	-	0.008
				core stored at Matachewan							
Downhole Tests											
	DDH ID	Depth	AZ	DIP							
	AT-08-005	18.00	89.90	-46.20							
	AT-08-005	51.00	90.00	-46.00							
	AT-08-005	102.00	90.20	-45.70							
	AT-08-005	147.00	88.70	-45.50							

Opawica Explorations Inc.

Atikwa Property UTM GRID LOCATION: Atikwa Lake Area, Ontario
 DDH#: AT-08-006 453242.1 E DRILL COMPANY: DOWNING
 Az 90.00 5474654.69 N GRID: Local, Metric:
 DIP -45.00 ZONE 15 E 2575.00
 E.O.H: 162 m NAD 83 N 1200.00
 Elev.: 382.31

Start: February 03, 2008; End: February 04, 2008

DDH#: AT-08-006

Drill Company: Claim: K15376
 Downing: NQ Core
 Logged by: FRED SHARPLEY

					Fred Sharpley						
From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
0.00	2.50	OVBD		casing left in hole							
2.50	8.30	Diorite		dark green, medium grained, massive uniform							
8.30	19.80	FZ		strongly sheared at 10-20 CA; scattered quartz veins at 20 CA; chlorite sericite alteration							
19.80	23.10	MF		medium greenish-grey, very fine grained, massive, uniform							
23.10	33.20	FZ		strongly sheared at 20 CA; chlorite sericite alteration							
					49857	7.50	8.30	0.80	0.02	-	0.035
					49858	8.30	9.00	0.70	0.005	-	0.004
					49859	9.00	10.00	1.00	0.005	-	0.001
					49860	10.00	11.00	1.00	0.005	-	0.002
					49861	11.00	12.00	1.00	0.005	-	0.002
					49862	12.00	13.00	1.00	0.005	0.005	0.009
					49863	13.00	14.00	1.00	0.005	-	0.003
					49864	14.00	15.00	1.00	0.005	-	0.001
					49865	15.00	16.00	1.00	0.005	-	0.003
					49866	Standard	53Pb		0.63	-	0.55
					49867	16.00	17.00	1.00	0.005	-	0.005
					49868	17.00	18.00	1.00	0.005	-	0.001

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
					49869	18.00	19.00	1.00	0.005	-	0.005
					49870	19.00	19.80	0.80	0.005	-	0.006
					49871	19.80	20.50	0.70	0.01	-	0.018
33.20	47.30	FP		buff color, fine grained, massive uniform, scattered quartz veining	49872	31.00	32.00	1.00	0.005	-	0.027
					49873	32.00	33.00	1.00	0.02	-	0.033
					49874	Dup			0.02	-	0.032
					49875	Blank			0.005	-	0.001
					49876	33.00	34.00	1.00	0.01	-	0.033
					49877	34.00	35.00	1.00	0.005	-	0.006
					49878	35.00	36.00	1.00	0.005	0.005	0.003
					49879	36.00	37.00	1.00	0.005	-	0.004
					49880	37.00	38.00	1.00	0.005	-	0.002
				38.0-39.0 20% core recovery	49881	38.00	39.00	1.00	0.005	-	0.002
					49882	39.00	40.00	1.00	0.005	-	0.001
					49883	40.00	41.00	1.00	0.005	-	0.006
					49884	41.00	42.00	1.00	0.005	-	0.002
					49885	Standard	54Pa		2.85	-	1.49
					49886	42.00	43.00	1.00	0.005	-	0.001
					49887	43.00	44.00	1.00	0.005	-	0.004
					49888	44.00	45.00	1.00	0.005	-	0.003
					49889	45.00	46.00	1.00	0.005	-	0.003
					49890	46.00	46.50	0.50	0.005	-	0.002
					49891	46.50	47.30	0.80	0.005	-	0.002
47.30	52.80	FZ		strongly sheared at 20 CA;	49892	47.30	48.00	0.70	0.005	-	0.003
					49893	48.00	49.00	1.00	0.005	-	0.001
					49894	Dup			0.005	-	0.001
					49895	Blank			0.005	-	0.001
52.80	59.60	MF		light to medium grey, massive							
59.60	69.50	Dio		Diorite: medium greenish-grey, medium grained, massive; traces pyrite	49896	59.60	60.00	0.40	0.09	0.07	0.081
					49897	60.00	61.00	1.00	0.07	-	0.066
					49898	61.00	62.00	1.00	0.05	-	0.063
					49899	62.00	63.00	1.00	0.09	-	0.07
					49900	63.00	64.00	1.00	0.10	-	0.044
					49901	64.00	65.00	1.00	0.03	-	0.037
					49902	65.00	66.00	1.00	0.04	-	0.058
					49903	Standard	52Pb		0.33	-	0.335
					49904	66.00	67.00	1.00	0.08	-	0.06

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
69.50	78.25	FP		light grey, medium grained white phenocrysts in fine grained groundmass; contact at 70 CA	49905	112.00	112.60	0.60	0.01	-	0.06
					49906	112.60	113.10	0.50	0.005	-	0.006
78.25	85.05	Dio		as above: fine grained, massive; traces po-py	49907	113.10	114.00	0.90	0.01	-	0.025
					49908	114.00	115.10	1.10	0.005	0.005	0.001
85.05	99.25	FP		as above:	49909	115.10	116.00	0.90	0.005	-	0.001
					49910	116.00	117.00	1.00	0.005	-	0.005
					49911	Dup			0.005	-	0.004
					49912	Blank			0.005	-	0.001
99.25	104.50	Dio		as above: fine grained, massive							
104.50	105.90	FP		as above:							
105.90	107.40	Dio		as above: probably coarse grained flow; rare spots							
107.40	108.40	FP		as above: fine grained							
108.40	112.60	Dio		as above: rare spots							
112.60	113.10	FP		as above: fine grained							
113.10	115.10	Gab		Gabbro: medium grained, massive							
115.10	116.00	FZ		moderately to strongly sheared at 70 CA; minor quartz veining							
116.00	117.00	Gab		as above:							
117.00	120.85	Dio		as above: fine grained; rare spots							
120.85	121.60	FP		as above: fine grained, massive							
121.60	141.96	Dio		as above: rare spots							
141.96	142.44	FP		as above: coarse grained							
142.44	150.20	Dio		as above: fine to medium grained							
150.20	151.35	FP		as above: fine grained							
151.35	162.00	Gab		as above:medium grained; rare spots							

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
				EOH							
				core stored at Matachewan							
Downhole Tests											
	DDH ID	Depth	AZ	DIP							
	AT-08-06	18	91.3	-44.7							
	AT-08-06	51	92.4	-44.8							
	AT-08-06	105	93.6	-44.8							
	AT-08-06	150	92.2	-44.3							

Opawica Explorations Inc.

Atikwa Property UTM GRID LOCATION: Atikwa Lake Area, Ontario
 DDH#: AT-08-007 453116.86 E DRILL COMPANY: DOWNING
 Az 90.00 5474455.86 N GRID: Local, Metric:
 DIP -45.00 ZONE 15 E 2465.00
 E.O.H: 252 m NAD 83 N 1000.00
 Elev.: 382.32 m

DDH#: AT-08-007

Drill Company: Claim: K15373
 Downing: NQ Core
 Logged by: FRED SHARPLEY

Start: February 04, 2008; End: February 08, 2008

Fred Sharpley

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
0.00	4.90	OVBD		casing left in hole							
4.90	8.25	MF		medium greenish grey, very fine grained, massive							
8.25	17.95	FP		coarse grained phenocrysts in medium grained groundmass							
17.95	19.76	MF		as above: massive							
19.76	21.15	FP		as above: contact at 60-80 CA							
21.15	25.60	MF-Bx		flow top breccia							
					49913	18.00	19.00	1.00	1.13	1.24	0.065
					49914	19.00	19.76	0.76	0.08	-	0.028
					49915	19.76	20.50	0.74	0.005	-	0.01
					49916	20.50	21.15	0.65	0.20	-	0.008
					49917	21.15	22.00	0.85	0.02	-	0.01
					49918	22.00	23.00	1.00	0.34	0.18	0.024
					49919	23.00	24.00	1.00	0.44	-	0.029
					49920	24.00	25.00	1.00	0.17	-	0.043
					49921	25.00	25.60	0.60	0.37	-	0.051
					49922	Standard	53PB		0.61	-	0.54
25.60	34.53	MF		as above: massive; traces of po	49923	25.60	26.00	0.40	0.24	-	0.024
					49924	26.00	27.00	1.00	0.19	0.23	0.017
					49925	27.00	28.00	1.00	3.77	3.63	0.058
					49926	28.00	29.00	1.00	0.31	-	0.041
					49927	29.00	30.00	1.00	0.25	-	0.03
					49928	30.00	31.00	1.00	0.31	-	0.042
					49929	31.00	32.00	1.00	0.21	-	0.048

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
					49930	32.00	33.00	1.00	0.89	-	0.044
					49931	Dup			0.89	-	0.044
					49932	Blank			0.01	-	0.001
					49933	33.00	34.00	1.00	0.04	-	0.035
					49934	34.00	34.53	0.53	0.02	-	0.018
34.53	38.30	FP		light grey, fine grained	49935	34.53	35.00	0.47	0.02	-	0.004
					49936	35.00	36.00	1.00	0.005	-	0.007
					49937	36.00	37.00	1.00	0.13	0.06	0.016
38.30	39.60	MF		as above: massive; traces of po	49938	37.00	37.50	0.50	0.01	-	0.011
					49939	37.50	38.30	0.80	0.01	-	0.008
39.60	58.10	Diorite		dark greenish-grey, fine grained: massive; probably coarser grained flow	49940	38.30	39.00	0.70	0.02	-	0.032
					49941	39.00	39.60	0.60	0.03	-	0.036
					49942	Standard	54Pa		2.88	-	1.49
					49943	39.60	40.00	0.40	0.01	-	0.006
					49944	40.00	41.00	1.00	0.08	-	0.02
					49945	41.00	42.00	1.00	0.08	-	0.013
					49946	42.00	43.00	1.00	0.13	-	0.037
					49947	43.00	44.00	1.00	0.10	-	0.029
					49948	44.00	45.00	1.00	0.08	0.09	0.029
					49949	45.00	46.00	1.00	0.09	-	0.025
					49950	46.00	47.00	1.00	0.03	-	0.022
					49951	Dup			0.04	-	0.025
					49952	Blank			0.005	-	0.003
					49953	47.00	48.00	1.00	0.06	-	0.03
					49954	48.00	49.00	1.00	0.01	-	0.023
					49955	49.00	50.00	1.00	0.01	-	0.015
					49956	50.00	51.00	1.00	0.53	-	0.034
					49957	51.00	52.00	1.00	0.04	-	0.03
					49958	52.00	53.00	1.00	0.03	-	0.027
					49959	53.00	54.00	1.00	0.08	-	0.055
					49960	54.00	55.00	1.00	0.03	0.03	0.093
					49961	55.00	56.00	1.00	0.04	-	0.14
					49962	Standard	52Pb		0.30	-	0.337
					49963	56.00	57.00	1.00	0.11	-	0.085
					49964	57.00	58.10	1.10	0.16	-	0.116
58.10	59.60	MF		as above: massive	49965	58.10	59.00	0.90	0.02	-	0.019
					49966	59.00	59.60	0.60	0.04	-	0.014
59.60	62.40	Diorite		as above:	49967	59.60	60.00	0.40	0.30	-	0.069
					49968	60.00	61.00	1.00	0.16	-	0.106
					49969	61.00	62.00	1.00	2.54	2.47	0.225
					49970	62.00	62.40	0.40	1.68	-	0.086
					49971	Dup			1.37	-	0.084
					49972	Blank			0.01	-	0.004

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
62.40	65.10	MF		spotted	49973	62.40	63.00	0.60	0.08	-	0.011
					49974	63.00	64.00	1.00	0.09	-	0.008
					49975	64.00	65.10	1.10	3.05	3.29	0.258
65.10	68.00	Diorite		as above:	49976	65.10	66.00	0.90	0.21	-	0.11
					49977	66.00	67.00	1.00	0.07	-	0.084
					49978	67.00	68.00	1.00	0.10	-	0.031
68.00	69.30	MF		massive	49979	68.00	68.50	0.50	0.15	-	0.021
					49980	68.50	69.30	0.80	0.01	-	0.005
69.30	71.10	Diorite		as above:	49981	69.30	70.00	0.70	0.33	-	0.038
					49982	Standard	53Pb		0.60	-	0.54
					49983	70.00	71.10	1.10	0.03	-	0.042
71.10	72.30	MF		as above: massive	49984	71.10	72.30	1.20	0.01	0.01	0.002
					49985	72.30	73.00	0.70	0.04	-	0.077
72.30	75.20	Diorite		as above:	49986	73.00	74.00	1.00	0.12	-	0.082
					49987	74.00	75.20	1.20	0.05	-	0.085
75.20	79.40	MF		as above: massive	49988	75.20	76.00	0.80	0.005	-	0.009
					49989	76.00	77.00	1.00	0.005	-	0.01
					49990	77.00	78.00	1.00	0.005	-	0.009
					49991	Dup			0.005	-	0.009
					49992	Blank			0.005	-	0.001
					49993	78.00	79.00	1.00	0.005	-	0.01
					49994	79.00	79.40	0.40	0.005	-	0.011
79.40	80.80	FP		coarse white phenocrysts in fine groundmass	49995	79.40	80.00	0.60	0.005	-	0.038
					49996	80.00	80.80	0.80	0.07	0.07	0.07
80.80	89.30	MF		as above: massive	49997	80.80	81.50	0.70	0.005	-	0.216
					49998	81.50	82.00	0.50	0.02	-	0.137
					49999	82.00	83.00	1.00	0.11	0.17	0.155
					50000	83.00	84.00	1.00	0.02	-	0.086
					50001	84.00	85.00	1.00	0.005	-	0.014
					50002	Standard	52Pb		0.31	-	0.337
					50003	85.00	86.00	1.00	0.005	-	0.024
					50004	86.00	87.00	1.00	0.005	-	0.01
					50005	87.00	88.00	1.00	0.005	0.005	0.008
					50006	88.00	88.50	0.50	0.005	-	0.006
					50007	88.50	89.30	0.80	0.005	-	0.004
89.30	91.40	FZ		strongly sheared at 40 CA; numerous quartz carbonate veins	50008	89.30	90.00	0.70	0.005	-	0.001
					50009	90.00	91.00	1.00	0.005	-	0.01
					50010	91.00	91.40	0.40	0.005	-	0.011
					50011	Dup			0.01	-	0.012
					50012	Blank			0.005	-	0.001
91.40	94.55	MF		as above: massive	50013	91.40	92.00	0.60	0.01	-	0.05
					50014	92.00	93.00	1.00	0.005	0.005	0.007
					50015	93.00	94.00	1.00	0.005	-	0.002

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
94.55	95.50	FP		coarse grained phenocrysts	50016	94.00	94.55	0.55	0.005	-	0.008
					50017	94.55	95.50	0.95	0.005	-	0.027
					50018	95.50	96.00	0.50	0.14	0.14	0.171
95.50	102.80	Diorite		as above:	50019	96.00	97.00	1.00	0.26	0.29	0.207
					50020	97.00	98.00	1.00	0.02	-	0.13
					50021	98.00	99.00	1.00	0.02	-	0.072
					50022	Standard	53Pb		0.63	-	0.55
					50023	99.00	100.00	1.00	0.14	-	0.053
					50024	100.00	101.00	1.00	0.01	-	0.053
					50025	101.00	102.00	1.00	0.005	-	0.004
					50026	102.00	102.80	0.80	0.01	-	0.035
102.80	103.15	FP		as above: fine grained	50027	102.80	103.15	0.35	0.005	-	0.065
103.15	109.50	Diorite		as above: medium grained	50028	103.15	104.00	0.85	0.03	0.04	0.039
					50029	104.00	105.00	1.00	0.01	-	0.065
					50030	105.00	106.00	1.00	0.01	-	0.044
					50031	Dup			0.02	-	0.042
					50032	Blank			0.01	-	0.002
					50033	106.00	107.00	1.00	0.01	-	0.016
109.50	110.10	FP		as above	50034	127.15	128.00	0.85	0.005	-	0.004
110.10	117.90	Dio		as above	50035	128.00	129.00	1.00	0.005	-	0.004
117.90	124.50	FP		as above	50036	129.00	130.00	1.00	0.005	-	0.054
124.50	126.20	Dio		as above	50037	130.00	131.00	1.00	0.01	-	0.054
					50038	131.00	132.00	1.00	0.005	-	0.074
					50039	132.00	133.00	1.00	0.01	0.01	0.112
					50040	133.00	133.80	0.80	0.005	-	0.073
					50041	Standard	54Pa		2.86	-	1.49
126.20	127.15	FP		as above	50042	136.45	137.00	0.55	0.005	-	0.033
127.15	133.80	Dio		as above: traces po	50043	137.00	138.00	1.00	0.005	-	0.034
133.80	136.45	FP		as above	50044	138.00	139.00	1.00	0.01	-	0.046
136.45	146.10	Dio		as above: traces po	50045	139.00	140.00	1.00	0.01	-	0.042
					50046	140.00	141.00	1.00	0.02	-	0.054
					50047	141.00	142.00	1.00	0.005	-	0.042
					50048	142.00	143.00	1.00	0.005	-	0.048
					50049	143.00	144.00	1.00	0.005	-	0.037
					50050	Dup			0.01	-	0.039
					50051	Blank			0.005	-	0.003
					50052	144.00	145.00	1.00	0.03	-	0.086
					50053	145.00	146.10	1.10	0.01	0.005	0.075
146.10	147.90	FP		as above: fine grained							
147.90	164.80	Dio		as above	50054	147.90	148.50	0.60	0.01	-	0.046
					50055	148.50	149.00	0.50	0.005	-	0.037
					50056	149.00	150.00	1.00	0.005	-	0.034

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
					50057	150.00	151.00	1.00	0.01	-	0.063
					50058	151.00	152.00	1.00	0.02	-	0.054
					50059	Standard	52Pb		0.31	-	0.335
					50060	152.00	153.00	1.00	0.02	-	0.061
					50061	153.00	154.00	1.00	0.11	-	0.12
					50062	154.00	155.00	1.00	0.06	-	0.052
					50063	155.00	156.00	1.00	0.01	-	0.047
					50064	156.00	157.00	1.00	0.02	0.02	0.056
					50065	157.00	158.00	1.00	0.005	-	0.131
					50066	158.00	159.00	1.00	0.16	-	0.126
					50067	159.00	160.00	1.00	0.02	-	0.062
					50068	Dup			0.005	-	0.063
					50069	Blank			0.005	-	0.002
					50070	160.00	161.00	1.00	0.02	-	0.103
					50071	161.00	162.00	1.00	0.09	0.09	0.101
					50072	162.00	163.00	1.00	0.02	-	0.023
					50073	163.00	164.00	1.00	0.01	-	0.034
					50074	164.00	164.80	0.80	0.01	-	0.019
164.80	166.30	FP		as above	50075	164.80	165.50	0.70	0.01	-	0.028
					50076	165.50	166.00	0.50	0.01	-	0.026
					50077	166.00	166.30	0.30	0.03	-	0.027
166.30	171.20	Dio		as above	50078	166.30	167.00	0.70	0.01	-	0.003
					50079	Standard	53Pb		0.61	-	0.55
					50080	167.00	168.00	1.00	0.01	-	0.004
					50081	168.00	169.00	1.00	0.02	-	0.037
					50082	169.00	170.00	1.00	0.01	-	0.031
					50083	170.00	171.20	1.20	0.03	-	0.06
171.20	172.60	FP		as above	50084	171.20	172.00	0.80	0.005	-	0.005
					50085	172.00	172.60	0.60	0.005	-	0.012
172.60	182.80	FT		Felsic Tuff: light grey, fine grained, foliated at 60 CA scattered quartz veins	50086	172.60	173.00	0.40	0.03	-	0.023
					50087	173.00	174.00	1.00	0.01	-	0.011
					50088	Dup			0.01	0.01	0.011
					50089	Blank			0.005	-	0.001
					50090	174.00	175.00	1.00	0.01	-	0.046
					50091	175.00	176.00	1.00	0.04	-	0.142
					50092	176.00	177.00	1.00	0.01	-	0.03
					50093	177.00	178.00	1.00	0.01	-	0.027
					50094	178.00	179.00	1.00	0.005	0.01	0.011
					50095	179.00	180.00	1.00	0.04	-	0.008
					50096	180.00	181.00	1.00	0.005	-	0.007
					50097	181.00	182.00	1.00	0.005	-	0.008
					50098	182.00	182.80	0.80	0.02	0.01	0.011

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
					50099	Standard	54Pa		2.85	-	1.48
182.80	191.90	Dio		as above: spotted	50100	182.80	183.50	0.70	0.005	-	0.004
					50101	183.50	184.00	0.50	0.02	-	0.013
					50102	184.00	185.00	1.00	0.02	-	0.021
					50103	185.00	186.00	1.00	0.01	-	0.009
					50104	186.00	187.00	1.00	0.005	-	0.003
					50105	187.00	188.00	1.00	0.005	-	0.007
					50106	188.00	189.00	1.00	0.03	-	0.016
					50107	189.00	190.00	1.00	0.02	0.03	0.023
					50108	Dup			0.02	-	0.022
					50109	Blank			0.005	-	0.002
					50110	190.00	191.00	1.00	0.005	-	0.022
					50111	191.00	191.90	0.90	0.01	-	0.005
191.90	193.40	FP		as above	50112	191.90	192.50	0.60	0.005	-	0.004
					50113	192.50	193.00	0.50	0.005	0.005	0.004
					50114	193.00	193.40	0.40	0.02	-	0.007
193.40	194.85	Dio		as above: spotted	50115	193.40	194.00	0.60	0.005	-	0.028
					50116	194.00	194.85	0.85	0.005	-	0.013
194.85	203.60	FP		as above							
				dark green, medium grained, massive, as above: spotted							
203.60	214.70	Gab			50117	203.60	204.00	0.40	0.005	-	0.003
					50118	Standard	52Pb		0.33	-	0.337
					50119	204.00	205.00	1.00	0.005	-	0.009
					50120	205.00	206.00	1.00	0.005	-	0.01
					50121	206.00	207.00	1.00	0.01	-	0.042
					50122	207.00	208.00	1.00	0.005	-	0.008
					50123	208.00	209.00	1.00	0.01	-	0.021
					50124	209.00	210.00	1.00	0.01	-	0.016
					50125	210.00	211.00	1.00	0.02	-	0.01
					50126	211.00	212.00	1.00	0.20	-	0.017
					50127	Dup			0.12	-	0.018
					50128	Blank			0.01	-	0.002
214.70	215.60	FP		as above:							
215.60	227.20	Gab		as above: spotted							
227.20	229.60	FP		as above							
229.60	231.80	Gab		massive							
231.80	232.40	FP		as above							
232.40	235.90	Gab		massive							

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
235.90	238.80	FP		as above							
238.80	241.70	Gab		massive							
241.70	242.60	FP		as above							
242.60	245.00	Gab		massive							
245.00	246.70	FP		as above							
246.70	249.40	Gab		massive							
249.40	249.95	FP		as above							
249.95	252.00	Gab		massive							
				EOH							
				core stored at Matachewan							
Downhole Tests											
	DDH ID	Depth	AZ	DIP							
	AT-08-07	18	90.4	-44.1							
	AT-08-07	54	90.3	-43.8							
	AT-08-07	102	92	-43.6							
	AT-08-07	150	89.6	-43							
	AT-08-07	201	88.2	-42.5							
	AT-08-07	250	88.3	-42.1							

Opawica Explorations Inc.

Atikwa Property UTM GRID LOCATION: Atikwa Lake Area, Ontario
 DDH#: AT-08-008 452928.94 E DRILL COMPANY: DOWNING
 Az 90.00 5474259.8 N GRID: Local, Metric:
 DIP -45.00 ZONE 15 E 2275.00
 E.O.H: 351.00 NAD 83 N 800.00
 Elev.: 399.21 Start: February 08, 2008; End: February 14, 2008

DDH#: AT-08-008

Drill Company: Claim: K15374
 Downing: NQ Core
 Logged by: FRED SHARPLEY

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
0.00	4.00	OVBD		casing left in hole							
4.00	27.20	PF		Pillowed Flow: dark green, very fine grained, spotted, pillow salvage with scattered pyrrhotite and chalcopyrite	50129	4.00	5.00	1.00	0.005	-	0.015
					50130	5.00	6.00	1.00	0.07	-	0.089
					50131	6.00	7.00	1.00	1.18	-	0.039
					50132	7.00	8.00	1.00	0.06	-	0.019
					50133	8.00	9.00	1.00	0.19	-	0.083
					50134	9.00	10.00	1.00	4.70	5.35	0.159
					50135	10.00	11.00	1.00	0.97	-	0.195
					50136	11.00	12.00	1.00	0.23	-	0.033
					50137	12.00	13.00	1.00	0.81	-	0.129
					50138	Standard	53Pb		0.62	-	0.540
					50139	13.00	14.00	1.00	7.75	5.83	0.477
					50140	14.00	15.00	1.00	0.04	-	0.066
					50141	15.00	16.00	1.00	0.02	-	0.011

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
					50142	16.00	17.00	1.00	0.02	-	0.132
					50143	17.00	18.00	1.00	0.07	-	0.110
					50144	18.00	19.00	1.00	0.03	-	0.216
					50145	19.00	20.00	1.00	0.01	-	0.066
					50146	20.00	21.00	1.00	0.01	-	0.014
					50147	Dup			0.01	-	0.014
					50148	Blank			0.005	-	0.002
					50149	21.00	22.00	1.00	0.005	-	0.018
					50150	22.00	23.00	1.00	0.005	-	0.007
					50151	23.00	24.00	1.00	0.06	-	0.026
					50152	24.00	25.00	1.00	0.01	-	0.006
					50153	25.00	26.00	1.00	0.68	0.58	0.590
					50154	26.00	26.50	0.50	0.16	-	0.025
					50155	26.50	27.20	0.70	0.02	-	0.022
					50156	27.20	28.00	0.80	0.01	-	0.006
27.20	33.00	FP		light grey, medium grained, contact at 20-70 CA	50157	28.00	29.00	1.00	0.005	-	0.005
					50158	Standard	54Pa		2.88	-	1.490
					50159	29.00	30.00	1.00	0.01	-	0.003
					50160	30.00	31.00	1.00	0.05	-	0.005
					50161	31.00	32.00	1.00	0.01	-	0.006
					50162	32.00	33.00	1.00	0.005	0.005	0.008
					50163	33.00	33.50	0.50	0.01	-	0.048
33.00	34.20	PF		as above: spotted,	50164	33.50	34.20	0.70	0.005	-	0.036
					50165	34.20	35.00	0.80	0.02	-	0.026
34.20	35.00	FP		as above:	50166	35.00	36.00	1.00	0.005	-	0.059
					50167	Dup			0.005	-	0.055
35.00	39.70	PF		as above: spotted, scattered po-cpy	50168	Blank			0.005	-	0.002
					50169	36.00	37.00	1.00	0.01	-	0.065
					50170	37.00	38.00	1.00	0.01	-	0.085
					50171	38.00	39.00	1.00	0.005	-	0.037
					50172	39.00	39.70	0.70	0.005	-	0.045
39.70	52.70	FP		as above	50173	39.70	40.50	0.80	0.005	0.01	0.004
52.70	53.26	MF		massive	50174	67.00	67.40	0.40	0.005	-	0.004
					50175	67.40	68.00	0.60	0.11	-	0.510
53.26	54.70	FP		as above	50176	68.00	69.00	1.00	0.005	-	0.008
					50177	Standard	52Pb		0.32	-	0.337
54.70	55.50	MF		massive	50178	69.00	70.00	1.00	0.08	-	0.031
					50179	70.00	71.00	1.00	0.08	-	0.062
55.50	58.25	FP		massive	50180	71.00	72.00	1.00	0.10	-	0.126

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
58.25	59.04	Gab		Gabbro: medium grained, massive	50181	72.00	73.00	1.00	0.05	-	0.055
					50182	73.00	74.00	1.00	2.30	2.23	0.052
					50183	74.00	75.00	1.00	0.04	-	0.016
59.04	67.40	FP		as above	50184	75.00	76.00	1.00	0.005	-	0.017
				61.04-62.26 diorite: fine grained	50185	76.00	77.00	1.00	0.03	-	0.023
67.40	73.00	PF		pillowed, spotted, minor cpy, po	50186	Dup			0.03	-	0.023
					50187	Blank			0.005	-	0.002
73.00	87.54	MFS		massive, spotted	50188	77.00	78.00	1.00	0.03	-	0.016
87.54	88.30	FP		as above: fine grained	50189	104.00	105.06	1.06	0.005	-	0.005
					50190	105.06	106.00	0.94	0.005	-	0.011
88.30	92.00	MFS		massive: spotted	50191	106.00	107.00	1.00	0.01	-	0.008
					50192	107.00	108.00	1.00	0.02	-	0.015
92.00	105.06	MF		massive:	50193	108.00	109.00	1.00	0.03	-	0.042
					50194	109.00	110.00	1.00	0.13	-	0.139
105.06	107.00	MFS		massive, spotted	50195	110.00	111.00	1.00	0.03	-	0.036
					50196	Standard	53Pb		0.62	-	0.550
107.00	134.00	MFV		mafic flow-vesicular: chalcopyrite, pyrrhotite in vesicles and fractures, 2-3mm; otherwise carbonate; rare pillow	50197	111.00	112.00	1.00	0.14	-	0.064
					50198	112.00	113.00	1.00	0.13	-	0.066
					50199	113.00	114.00	1.00	0.55	-	0.283
					50200	114.00	115.00	1.00	0.36	-	0.336
					50201	115.00	116.00	1.00	0.69	0.82	0.820
					50202	116.00	117.00	1.00	0.19	0.16	0.207
					50203	117.00	118.00	1.00	0.19	-	0.139
					50204	118.00	119.00	1.00	0.34	-	0.206
					50205	Dup			0.21	-	0.191
					50206	Blank			0.005	-	0.004
					50207	119.00	120.00	1.00	0.15	-	0.127
					50208	120.00	121.00	1.00	0.12	-	0.181
					50209	121.00	122.00	1.00	0.82	0.70	0.331
					50210	122.00	123.00	1.00	0.41	-	0.520
					50211	123.00	124.00	1.00	0.66	-	0.448
					50212	124.00	125.00	1.00	0.08	-	0.052
					50213	125.00	126.00	1.00	0.07	-	0.050
					50214	126.00	127.00	1.00	0.10	0.11	0.062
					50215	127.00	128.00	1.00	0.12	-	0.080
					50216	Standard	54Pa		2.85	-	1.480
					50217	128.00	129.00	1.00	0.03	-	0.046

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
					50218	129.00	130.00	1.00	0.01	-	0.005
					50219	130.00	131.00	1.00	0.08	-	0.027
					50220	131.00	132.00	1.00	0.16	-	0.033
					50221	132.00	133.00	1.00	0.26	-	0.092
					50222	133.00	134.00	1.00	0.11	-	0.071
134.00	139.80	MF-Bx		mafic flow-beccia: chalcopyrite, pyrrhotite in matrix and fractures,	50223	134.00	135.00	1.00	0.22	-	0.112
					50224	135.00	136.00	1.00	0.22	-	0.158
					50225	Dup			0.17	-	0.157
					50226	Blank			0.005	-	0.005
					50227	136.00	137.00	1.00	0.35	-	0.510
					50228	137.00	138.00	1.00	0.06	-	0.086
					50229	138.00	139.00	1.00	0.02	-	0.030
139.80	140.76	FP		as above:	50230	139.00	140.00	1.00	0.005	-	0.006
					50231	140.00	141.00	1.00	0.005	0.01	0.007
140.76	142.24	MF-Bx		as above:	50232	141.00	142.00	1.00	0.01	-	0.012
142.24	144.13	FP		as above:	50233	142.00	143.00	1.00	0.005	-	0.007
					50234	143.00	144.00	1.00	0.01	-	0.013
					50235	144.00	145.00	1.00	0.02	-	0.008
					50236	Standard	52Pb		0.32	-	0.334
144.13	152.14	MF-Bx		as above:	50237	145.00	146.00	1.00	0.08	-	0.061
					50238	146.00	147.00	1.00	0.13	-	0.066
					50239	147.00	148.00	1.00	0.06	-	0.029
					50240	148.00	149.00	1.00	0.10	-	0.031
					50241	149.00	150.00	1.00	0.10	-	0.027
					50242	150.00	151.00	1.00	0.69	0.67	0.187
					50243	151.00	151.50	0.50	0.19	-	0.091
					50244	151.50	152.14	0.64	0.38	0.55	0.097
					50245	Dup			0.97	-	0.090
					50246	Blank			0.01	-	0.009
152.14	154.10	FP		coarse feldspar phenocrysts	50247	152.14	153.00	0.86	0.02	-	0.005
					50248	153.00	154.10	1.10	0.01	-	0.004
154.10	155.00	MF-Bx		as above: flow breccia	50249	154.10	155.00	0.90	0.38	-	0.159
					50250	155.00	156.00	1.00	0.40	-	0.090
155.00	159.80	MF		massive	50251	156.00	157.00	1.00	0.07	0.05	0.095
					50252	157.00	158.00	1.00	0.02	-	0.043
				moderate to strongly sheared at 60 CA; 20% quartz veining and disseminated po-cpy, 2-3%; sericite alteration, weak to moderate							
159.80	164.70	FZ			50253	158.00	159.00	1.00	0.01	-	0.018
					50254	159.00	159.80	0.80	0.005	-	0.012
					50255	159.80	160.50	0.70	0.14	-	0.143

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
					50256	Standard	53Pb		0.62	-	0.550
					50257	160.50	161.00	0.50	0.28	0.22	0.680
					50258	161.00	162.00	1.00	0.06	-	0.264
					50259	162.00	163.00	1.00	0.05	-	0.141
					50260	163.00	164.00	1.00	0.005	-	0.037
					50261	164.00	164.70	0.70	0.04	-	0.041
164.70	175.00	MF		as above: massive:	50262	164.70	165.50	0.80	0.005	-	0.009
					50263	165.50	166.00	0.50	0.01	-	0.013
					50264	166.00	167.00	1.00	0.01	-	0.040
					50265	Dup			0.01	-	0.044
					50266	Blank			0.005	-	0.002
					50267	167.00	168.00	1.00	0.01	-	0.020
					50268	168.00	169.00	1.00	0.01	-	0.004
					50269	169.00	170.00	1.00	0.005	-	0.011
					50270	170.00	171.00	1.00	0.005	-	0.026
					50271	171.00	172.00	1.00	0.01	-	0.006
					50272	172.00	173.00	1.00	0.01	0.01	0.013
					50273	173.00	174.00	1.00	0.01	-	0.022
					50274	174.00	175.00	1.00	0.005	-	0.045
175.00	177.03	FP		as above: fine grained	50275	175.00	176.00	1.00	0.005	-	0.013
					50276	Standard	54Pa		2.88	-	1.490
					50277	176.00	177.03	1.03	0.01	-	0.007
177.03	185.50	MFV		vesicular, scattered po-cpy in vesicles	50278	177.03	178.00	0.97	0.05	-	0.047
					50279	178.00	179.00	1.00	0.13	0.09	0.056
					50280	179.00	180.00	1.00	0.02	-	0.027
					50281	180.00	181.00	1.00	0.04	-	0.073
					50282	181.00	182.00	1.00	0.03	-	0.082
					50283	182.00	183.00	1.00	0.02	-	0.040
					50284	183.00	184.00	1.00	0.01	-	0.090
					50285	Dup			0.005	-	0.080
					50286	Blank			0.01	-	0.001
					50287	184.00	185.00	1.00	0.01	-	0.051
					50288	185.00	185.50	0.50	0.005	0.01	0.029
185.50	199.00	MF-Bx		mafic flow breccia; disseminated po-cpy	50289	185.50	186.00	0.50	0.01	-	0.030
					50290	186.00	187.00	1.00	0.02	-	0.051
					50291	187.00	188.00	1.00	0.01	-	0.040
					50292	188.00	189.00	1.00	0.06	-	0.036
					50293	189.00	190.00	1.00	0.005	-	0.060
					50294	190.00	191.00	1.00	0.04	-	0.048
					50295	191.00	192.00	1.00	0.04	-	0.082

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
					50296	Standard	50Pb		0.82	-	0.730
					50297	192.00	193.00	1.00	0.10	-	0.072
					50298	193.00	194.00	1.00	0.66	-	0.239
					50299	194.00	195.00	1.00	0.02	-	0.078
					50300	195.00	196.00	1.00	0.04	-	0.062
					50301	196.00	197.00	1.00	0.14	-	0.108
					50302	197.00	198.00	1.00	0.05	-	0.163
					50303	198.00	199.00	1.00	4.01	4.39	0.374
199.00	207.80	MF		as above: massive:	50304	199.00	200.00	1.00	1.71	1.68	0.147
					50305	Dup			2.40	-	0.155
					50306	Blank			0.01	-	0.002
					50307	200.00	201.00	1.00	0.01	-	0.032
					50308	201.00	202.00	1.00	0.01	-	0.036
					50309	202.00	203.00	1.00	0.005	0.02	0.056
					50310	203.00	204.00	1.00	0.005	-	0.004
					50311	204.00	205.00	1.00	0.01	-	0.014
					50312	205.00	206.00	1.00	0.005	-	0.015
					50313	206.00	207.00	1.00	0.02	-	0.054
					50314	207.00	207.80	0.80	0.005	-	0.030
207.80	210.10	FP		coarse feldspar phenocrysts	50315	207.80	208.50	0.70	0.005	-	0.007
					50316	Standard	54Pa		2.88	-	1.490
					50317	208.50	209.00	0.50	0.05	-	0.083
					50318	209.00	210.10	1.10	0.02	-	0.021
210.10	213.00	MF-Bx		flow-top-breccia: weak disseminated po-cpy	50319	210.10	211.00	0.90	0.02	-	0.049
					50320	211.00	212.00	1.00	0.03	-	0.031
					50321	212.00	213.00	1.00	0.01	-	0.011
213.00	215.23	MF-V		vesicular, scattered po-py in vesicles	50322	213.00	214.00	1.00	0.06	0.08	0.047
					50323	214.00	214.50	0.50	0.005	-	0.043
					50324	214.50	215.23	0.73	0.01	-	0.019
					50325	Dup			0.005	-	0.021
					50326	Blank			0.005	-	0.001
215.23	220.17	FP		coarse feldspar phenocrysts	50327	215.23	216.00	0.77	0.005	-	0.005
					50328	216.00	217.00	1.00	0.005	-	0.003
					50329	217.00	218.00	1.00	0.005	-	0.003
					50330	218.00	219.00	1.00	0.005	-	0.003
					50331	219.00	219.50	0.50	0.005	-	0.003
					50332	219.50	220.17	0.67	0.005	-	0.004
220.17	222.00	MF		massive	50333	220.17	221.00	0.83	0.005	-	0.007
					50334	221.00	222.00	1.00	0.005	-	0.017
222.00	224.00	MF-Bx		flow-top-breccia: weak disseminated po-cpy	50335	222.00	223.00	1.00	0.21	0.26	0.061

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
					50336	Standard	52Pb		0.33	-	0.334
					50337	223.00	224.00	1.00	0.03	-	0.043
224.00	229.85	MF		massive	50338	224.00	225.00	1.00	0.005	0.005	0.012
229.85	235.30	FP		white phenocrysts in a dioritic groundmass	50339	225.00	226.00	1.00	0.005	-	0.012
					50340	226.00	227.00	1.00	0.04	-	0.010
					50341	227.00	228.00	1.00	0.02	-	0.014
					50342	228.00	229.00	1.00	0.04	-	0.014
					50343	229.00	229.85	0.85	0.07	-	0.005
					50344	229.85	230.50	0.65	0.01	-	0.010
					50345	Dup			0.01	-	0.010
					50346	Blank			0.005	-	0.001
					50347	230.50	231.00	0.50	0.005	-	0.005
					50348	231.00	232.00	1.00	0.01	-	0.006
					50349	232.00	233.00	1.00	0.01	-	0.007
					50350	233.00	234.00	1.00	0.005	-	0.004
					50351	234.00	234.50	0.50	0.005	-	0.010
					50352	234.50	235.30	0.80	0.01	-	0.006
235.30	236.74	Dio		fine grained	50353	235.30	236.00	0.70	0.02	-	0.067
					50354	236.00	236.74	0.74	0.02	-	0.017
236.74	237.90	FP		as above:	50355	236.74	237.90	1.16	0.49	0.50	0.090
					50356	Standard	53Pb		0.61	-	0.540
237.90	251.70	Dio		as above	50357	237.90	238.50	0.60	0.02	-	0.013
251.70	253.70	FP		coarse grained phenocrysts	50358	247.00	248.00	1.00	0.01	-	0.016
					50359	248.00	249.00	1.00	0.03	-	0.046
253.70	264.88	Dio		fine to medium grained flow	50360	249.00	250.00	1.00	0.005	-	0.010
					50361	250.00	251.00	1.00	0.11	-	0.011
264.88	266.15	FP		coarse grained, as above	50362	251.00	251.80	0.80	0.05	-	0.013
					50363	251.80	252.50	0.70	0.14	-	0.025
266.15	268.50	Dio		as above	50364	Dup			0.12	-	0.026
					50365	Blank			0.01	-	0.002
268.50	272.00	FP		as above: fine grained							
272.00	276.60	Dio		as above: medium grained							
276.60	279.30	FP		as above: fine grained							
279.30	282.90	Dio		as above: medium grained,	50366	279.30	280.00	0.70	0.27	0.26	0.196
					50367	280.00	281.00	1.00	0.22	0.20	0.170
282.90	283.30	FZ		strongly sheared at 70 CA	50368	281.00	282.00	1.00	0.07	-	0.110

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
					50369	Standard	54Pa		2.88	-	1.480
					50370	282.00	282.90	0.90	0.04	-	0.110
					50371	282.90	283.30	0.40	0.01	-	0.002
283.30	283.50	Dio		as above: medium grained,	50372	283.30	283.80	0.50	0.05	-	0.064
283.50	284.40	FP		as above: fine grained	50373	304.50	305.34	0.84	0.34	0.57	0.009
					50374	305.34	306.00	0.66	0.05	-	0.045
284.40	288.15	Dio		as above: medium grained	50375	306.00	307.00	1.00	0.10	-	0.015
					50376	307.00	308.00	1.00	0.10	-	0.019
288.15	291.40	FP		as above: fine grained	50377	Dup			0.10	-	0.017
					50378	Blank			0.01	-	0.001
291.40	292.58	Dio		as above: medium grained	50379	308.00	309.00	1.00	0.04	-	0.021
					50380	309.00	310.00	1.00	0.08	-	0.029
292.58	293.90	FP		as above: medium grained	50381	310.00	311.00	1.00	0.03	-	0.031
					50382	311.00	312.00	1.00	0.01	-	0.032
293.90	299.60	Dio		as above: medium grained	50383	312.00	312.60	0.60	0.02	-	0.039
299.60	305.34	FP		as above: fine grained	50384	332.26	333.30	1.04	0.06	-	0.062
					50385	333.30	334.00	0.70	0.37	-	0.310
305.34	312.60	Dio		as above: medium grained	50386	334.00	335.00	1.00	0.21	-	0.170
					50387	Standard	52Pb		0.29	-	0.336
					50388	335.00	336.00	1.00	0.10	-	0.110
312.60	320.23	FP		as above:	50389	336.00	337.00	1.00	0.005	-	0.046
					50390	337.00	338.00	1.00	0.33	-	0.080
320.23	324.20	Dio		as above:	50391	338.00	339.00	1.00	0.42	0.41	0.120
					50392	339.00	340.00	1.00	0.27	-	0.080
324.20	329.60	FP		as above:	50393	340.00	341.00	1.00	0.24	-	0.090
					50394	341.00	342.00	1.00	0.11	-	0.226
329.60	333.30	Dio		as above:	50395	342.00	343.00	1.00	0.01	-	0.005
					50396	Dup			0.02	-	0.004
333.30	342.00	MF-Bx		medium to dark green, flow top bx: weak to moderate disseminated pyrrhotite	50397	Blank			0.01	-	0.001
				334.1-334.8 FP							
342.00	348.40	Dio		as above:							
348.40	351.00	FP		as above:							
				EOH							

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
				core stored at Matachewan							
Downhole Tests											
DDH ID	Depth	AZ	DIP								
AT-08-08	18	96.3	-44.8								
AT-08-08	51	94.8	-44.6								
AT-08-08	99	92	-44.2								
AT-08-08	150	91.6	-43.8								
AT-08-08	201	92	-43.3								
AT-08-08	252	91.2	-42.8								
AT-08-08	350	90	-41.6								

Opawica Explorations Inc.

Atikwa Property UTM GRID LOCATION: Atikwa Lake Area, Ontario
 DDH#: AT-08-009 452913.82 N DRILL COMPANY: DOWNING
 Az 90.00 5474150.4 E GRID: Local, Metric:
 DIP -45.00 ZONE 15 E 2265.00
 E.O.H: 426.00 NAD 83 N 700.00
 Elev.: 396.47 Start: February 16, 2008; End: February 22, 2008

Hole # AT-08-009
 Drill Company: Claim: K15374
 Downing: NQ Core
 Logged by: FRED SHARPLEY

Fred Sharpley											
From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
0.00	11.00	OVBD		casing left in hole							
11.00	15.46	MFS		Andesite spotted, massive							
15.46	18.00	PF		spotted with pillows							
18.00	19.30	MFS		massive with spotted							
19.30	30.26	PF		pillowed with breccia							
30.26	35.00	MFS		massive, spotted							
35.00	38.50	PF		pillowed							
38.50	40.00	FP		light grey, fine grained, minor gabbro							
40.00	49.90	PF		as above; pillowed, brecciated							
					50398	11.00	12.0	1.00	0.04	-	0.033
					50399	12.00	13.0	1.00	0.005	-	0.009
					50400	13.00	14.0	1.00	0.02	-	0.016
					50401	14.00	15.0	1.00	0.01	-	0.009
					50402	15.00	15.5	0.46	0.01	-	0.011
					50403	15.46	16.00	0.54	0.005	-	0.009
					50404	16.00	17.00	1.00	0.01	0.01	0.015
					50405	17.00	18.00	1.00	0.01	-	0.014
					50406	18.00	18.46	0.46	0.01	-	0.008
					50407	Standard	54Pa		2.81	-	1.490
					50408	18.46	19.30	0.84	0.005	-	0.007
					50409	19.30	20.00	0.70	0.005	-	0.023
					50410	20.00	21.00	1.00	0.01	-	0.020
					50411	21.00	22.00	1.00	0.01	0.02	0.022
					50412	22.00	23.00	1.00	0.01	-	0.014
					50413	23.00	24.00	1.00	0.005	-	0.015
					50414	24.00	25.00	1.00	0.01	-	0.005

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
					50415	25.00	26.00	1.00	0.01	-	0.012
					50416	Dup			0.01	-	0.012
					50417	Blank			0.005	-	0.001
					50418	26.00	27.00	1.00	0.005	-	0.010
					50419	27.00	28.00	1.00	0.01	-	0.008
					50420	28.00	29.00	1.00	0.01	-	0.009
					50421	29.00	29.50	0.50	0.01	-	0.009
					50422	29.50	30.26	0.76	0.02	0.01	0.022
					50423	30.26	31.00	0.74	0.01	-	0.003
					50424	31.00	32.00	1.00	0.02	-	0.012
					50425	32.00	33.00	1.00	0.01	-	0.012
					50426	33.00	34.00	1.00	0.01	-	0.007
					50427	Standard	54Pa		2.85	-	1.500
					50428	34.00	35.00	1.00	0.01	-	0.010
					50429	35.00	36.00	1.00	0.01	-	0.016
					50430	36.00	37.00	1.00	0.01	-	0.039
					50431	37.00	38.00	1.00	0.02	-	0.136
					50432	38.00	38.50	0.50	0.01	-	0.093
					50433	38.50	39.00	0.50	0.01	-	0.002
					50434	39.00	40.00	1.00	0.005	-	0.002
					50435	40.00	41.00	1.00	0.005	-	0.039
					50436	Dup			0.02	-	0.044
					50437	Blank			0.005	-	0.001
49.90	55.00	MFS		massive, spotted	50438	41.00	42.00	1.00	0.005	-	0.030
					50439	42.00	43.00	1.00	0.005	-	0.001
					50440	43.00	44.00	1.00	0.005	-	0.006
					50441	44.00	45.00	1.00	0.005	-	0.006
					50442	45.00	46.00	1.00	0.005	-	0.008
					50443	46.00	47.00	1.00	0.005	-	0.007
					50444	47.00	48.00	1.00	0.005	-	0.010
					50445	48.00	49.00	1.00	0.005	-	0.011
					50446	49.00	50.00	1.00	0.02	0.01	0.009
					50447	Standard	52Pb		0.30	-	0.337
					50448	50.00	51.00	1.00	0.005	-	0.007
					50449	51.00	52.00	1.00	0.005	-	0.017
					50450	52.00	53.00	1.00	0.005	-	0.011
					50451	53.00	54.00	1.00	0.005	-	0.018
					50452	54.00	55.00	1.00	0.01	-	0.010
55.00	55.77	FP		as above:	50453	55.00	56.00	1.00	0.005	-	0.010
					50454	56.00	57.00	1.00	0.005	-	0.013
55.77	72.75	MF		massive	50455	57.00	58.00	1.00	0.02	0.02	0.010
					50456	Dup			0.005	-	0.010
72.75	105.00	PF		pillowed, spotted; 10% carbonate veining	50457	Blank			0.005	-	0.001

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
					50458	58.00	59.00	1.00	0.01	-	0.009
					50459	59.00	60.00	1.00	0.01	-	0.010
					50460	72.00	72.75	0.75	0.005	-	0.005
					50461	72.75	73.50	0.75	0.01	0.005	0.007
					50462	73.50	74.00	0.50	0.02	-	0.057
					50463	74.00	75.00	1.00	0.005	-	0.016
					50464	75.00	76.00	1.00	0.005	-	0.022
					50465	76.00	77.00	1.00	0.005	-	0.021
					50466	Standard	50Pb		0.86	-	0.730
					50467	77.00	78.00	1.00	0.005	-	0.023
					50468	78.00	79.00	1.00	0.005	-	0.046
					50469	79.00	80.00	1.00	0.01	0.03	0.056
					50470	80.00	81.00	1.00	0.005	-	0.015
					50471	81.00	82.00	1.00	0.005	-	0.034
					50472	82.00	83.00	1.00	0.005	-	0.039
					50473	83.00	84.00	1.00	0.005	-	0.033
					50474	84.00	85.00	1.00	0.07	0.09	0.048
					50475	Dup			0.005	-	0.050
					50476	Blank			0.005	-	0.001
					50477	85.00	86.00	1.00	0.005	-	0.003
					50478	86.00	87.00	1.00	0.005	-	0.010
					50479	87.00	88.00	1.00	0.005	-	0.003
					50480	88.00	89.00	1.00	0.005	-	0.014
					50481	89.00	90.00	1.00	0.005	-	0.014
					50482	90.00	91.00	1.00	0.005	-	0.012
					50483	91.00	92.00	1.00	0.005	-	0.008
					50484	92.00	93.00	1.00	0.005	-	0.011
					50485	93.00	94.00	1.00	0.005	-	0.007
					50486	Standard	53Pb		0.64	-	0.540
					50487	94.00	95.00	1.00	0.005	-	0.006
					50488	95.00	96.00	1.00	0.005	-	0.006
					50489	96.00	97.00	1.00	0.005	-	0.002
					50490	97.00	98.00	1.00	0.005	-	0.014
					50491	98.00	99.00	1.00	0.005	-	0.007
					50492	99.00	100.00	1.00	0.06	0.04	0.011
					50493	100.00	101.00	1.00	0.005	-	0.010
					50494	101.00	102.00	1.00	0.005	-	0.011
					50495	Dup			0.005	-	0.011
					50496	Blank			0.005	-	0.001
					50497	102.00	103.00	1.00	0.03	-	0.014
					50498	103.00	104.00	1.00	0.01	-	0.006
					50499	104.00	105.00	1.00	0.01	-	0.010

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
105.00	122.74	MFS		massive, spotted	50500	105.00	106.00	1.00	0.005	-	0.009
					37501	106.00	107.00	1.00	0.01	0.01	0.012
					37502	107.00	108.00	1.00	0.005	-	0.011
				dark green, massive, uniform, coarse grained, pyroxene; possible gabbro							
122.74	137.35	Dio			37503	123.00	123.74	0.74	0.01	-	0.013
					37504	123.74	124.50	0.76	0.01	-	0.017
					37505	Standard	54Pa		2.78	-	1.490
137.35	142.80	MFS		as above:	37506	124.50	125.00	0.50	0.005	-	0.019
					37507	125.00	126.00	1.00	0.005	-	0.054
					37508	126.00	127.00	1.00	0.02	-	0.025
					37509	127.00	128.00	1.00	0.005	-	0.069
					37510	128.00	129.00	1.00	0.16	-	0.152
					37511	129.00	130.00	1.00	0.22	0.15	0.172
					37512	130.00	131.00	1.00	0.01	-	0.020
					37513	131.00	132.00	1.00	0.01	-	0.026
					37514	Dup		0.02	-	0.024	
					37515	Blank		0.005	-	0.001	
					37516	132.00	133.00	1.00	0.005	-	0.012
					37517	133.00	134.00	1.00	0.02	-	0.005
					37518	134.00	135.00	1.00	0.005	-	0.032
					37519	135.00	136.00	1.00	0.005	-	0.003
					37520	136.00	136.50	0.50	0.005	-	0.016
					37521	136.50	137.35	0.85	0.005	-	0.340
					37522	137.35	138.00	0.65	0.09	0.05	0.058
142.80	150.70	FP		as above: fine grained							
					37523	176.00	176.50	0.50	0.02	-	0.011
					37524	Standard	52PB		0.31	-	0.337
					37525	176.50	177.00	0.50	0.005	-	0.040
150.70	157.20	MF		as above: massive	37526	177.00	178.00	1.00	0.01	-	0.015
					37527	178.00	179.00	1.00	0.01	-	0.012
157.20	158.80	FP		as above: fine grained	37528	179.00	180.00	1.00	0.01	-	0.024
					37529	180.00	181.00	1.00	0.03	-	0.025
158.80	160.30	MFS		as above: spotted	37530	181.00	182.00	1.00	0.005	-	0.020
					37531	182.00	183.00	1.00	0.14	-	0.020
160.30	161.70	FP		as above:	37532	183.00	184.00	1.00	0.01	-	0.015
161.70	162.85	MFS		as above: massive, spotted	37533	Dup		0.005	-	0.014	
					37534	Blank		0.005	-	0.002	
162.85	163.40	FP		as above: fine grained	37535	184.00	185.00	1.00	0.005	-	0.004
					37536	185.00	186.00	1.00	0.005	-	0.026
163.40	175.25	MFV		massive, vesicular	37537	186.00	187.00	1.00	0.01	0.01	0.009
					37538	187.00	187.90	0.90	0.03	-	0.019
175.25	176.50	FP		fine grained: contact at 50 CA	37539	187.90	188.40	0.50	0.005	-	0.005

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
176.50	187.90	MFV		fine white vesicles, 10% carbonate	37540	188.40	189.60	1.20	0.005	-	0.007
					37541	189.60	190.00	0.40	0.02	-	0.028
					37542	190.00	191.00	1.00	0.01	-	0.055
187.90	188.40	FP		as above: fine	37543	191.00	192.00	1.00	0.005	-	0.012
					37544	Standard	50Pb		0.85	-	0.730
188.40	189.60	MFV		as above:	37545	192.00	192.65	0.65	0.005	-	0.036
					37546	192.65	193.50	0.85	0.005	-	0.016
189.60	192.65	FZ		strongly sheared at 80 CA; bleached, silicified, minor pyrrhotite, pyrite, chalcopyrite	37547	193.50	194.00	0.50	0.005	-	0.015
					37548	194.00	195.00	1.00	0.005	0.005	0.011
192.65	197.86	MF-Bx		flow breccia; minor po	37549	195.00	196.00	1.00	0.005	-	0.012
					37550	196.00	197.00	1.00	0.02	-	0.009
197.86	200.36	FP		as above: fine grained	37551	197.00	198.00	1.00	0.005	-	0.012
					37552	198.00	198.50	0.50	0.005	-	0.010
200.36	208.60	MF-Bx		flow breccia: minor po	37553	Dup			0.005	-	0.009
					37554	Blank			0.005	-	0.001
208.60	211.90	FP		as above: fine	37555	198.50	199.00	0.50	0.005	-	0.009
					37556	199.00	199.50	0.50	0.005	-	0.009
					37557	199.50	200.36	0.86	0.005	-	0.009
					37558	200.36	201.00	0.64	0.005	-	0.009
					37559	201.00	202.00	1.00	0.005	-	0.019
					37560	202.00	203.00	1.00	0.005	-	0.040
					37561	203.00	204.00	1.00	0.005	0.005	0.022
					37562	204.00	205.00	1.00	0.005	-	0.013
					37563	205.00	206.00	1.00	0.005	-	0.014
					37564	Standard	53Pb		0.64	-	0.540
					37565	206.00	207.00	1.00	0.005	-	0.014
					37566	207.00	208.00	1.00	0.005	-	0.008
					37567	208.00	208.60	0.60	0.05	0.07	0.023
					37568	208.60	209.00	0.40	0.005	-	0.003
					37569	209.00	210.00	1.00	0.005	-	0.005
					37570	210.00	211.00	1.00	0.005	-	0.003
					37571	211.00	211.90	0.90	0.005	-	0.009
211.90	216.00	MFV		massive, vesicular, spotted	37572	211.90	212.50	0.60	0.01	-	0.053
					37573	Dup			0.02	-	0.057
216.00	222.05	FP		coarse grained, contact at 70 CA	37574	Blank			0.02	-	0.001
222.05	226.70	MF		massive	37575	232.00	233.00	1.00	0.01	-	0.014
					37576	233.00	234.00	1.00	0.05	-	0.016
226.70	232.00	FP		medium grained, dioritic	37577	234.00	235.00	1.00	0.01	-	0.020
232.00	237.70	MF-V		vesicular, massive	37578	235.00	236.00	1.00	0.005	-	0.013
237.70	243.00	MF-Bx		flow breccia; subrounded to angular fragments of light grey volcanics; weak disseminated pyrite	37579	236.00	237.00	1.00	0.04	-	0.019

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
					37580	237.00	238.00	1.00	0.03	-	0.018
					37581	238.00	239.00	1.00	0.005	-	0.013
					37582	239.00	240.00	1.00	0.03	0.03	0.011
					37583	Standard	54Pa		2.88	-	1.480
					37584	240.00	241.00	1.00	0.01	-	0.015
					37585	241.00	242.00	1.00	0.05	-	0.013
					37586	242.00	243.00	1.00	0.01	-	0.017
243.00	248.25	FP		fine grained, contact at 20 CA	37587	243.00	244.00	1.00	0.005	-	0.006
248.25	252.00	MF-Bx		flow breccia; traces po	37588	248.25	249.00	0.75	0.005	-	0.014
					37589	249.00	250.00	1.00	0.01	-	0.016
252.00	260.00	MF		massive	37590	250.00	251.00	1.00	0.01	-	0.017
					37591	Dup			0.01	-	0.018
260.00	266.00	MF-Bx		flow breccia	37592	Blank			0.005	-	0.002
					37593	251.00	252.00	1.00	0.005	-	0.016
266.00	267.80	MF		massive	37594	252.00	253.00	1.00	0.02	-	0.018
					37595	253.00	254.00	1.00	0.005	-	0.016
267.80	268.70	FP		medium grained	37596	254.00	255.00	1.00	0.03	-	0.012
					37597	255.00	256.00	1.00	0.02	-	0.012
268.70	273.20	MF		massive	37598	256.00	257.00	1.00	0.02	-	0.012
					37599	257.00	258.00	1.00	0.04	0.07	0.010
273.20	273.60	FP		as above: contact at 70 CA	37600	258.00	259.00	1.00	0.005	-	0.010
					37601	259.00	260.00	1.00	0.02	-	0.011
					37602	Standard	52Pb		0.32	-	0.338
273.60	276.50	MF-Bx		flow breccia	37603	260.00	261.00	1.00	0.05	-	0.013
					37604	261.00	262.00	1.00	0.005	-	0.011
276.50	278.10	FP		fine grained; contact at 80 CA	37605	262.00	263.00	1.00	0.005	-	0.019
					37606	263.00	264.00	1.00	0.005	-	0.025
					37607	264.00	265.00	1.00	0.005	-	0.016
					37608	265.00	266.00	1.00	0.02	-	0.011
					37609	266.00	267.00	1.00	0.02	-	0.016
					37610	267.00	267.80	0.80	0.04	0.03	0.014
					37611	Dup			0.02	-	0.014
					37612	Blank			0.01	-	0.002
					37613	267.80	268.70	0.90	0.02	-	0.007
					37614	268.70	269.50	0.80	0.01	-	0.014
					37615	269.50	270.00	0.50	0.01	-	0.009
					37616	270.00	271.00	1.00	0.005	-	0.010
					37617	271.00	272.00	1.00	0.01	-	0.004
					37618	272.00	272.50	0.50	0.005	-	0.011
					37619	272.50	273.20	0.70	0.005	-	0.007
					37620	273.20	273.60	0.40	0.005	-	0.003
					37621	273.60	274.00	0.40	0.08	-	0.030

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
					37622	Standard	50Pb		0.84	-	0.730
					37623	274.00	275.00	1.00	0.05	-	0.018
					37624	275.00	276.00	1.00	0.01	-	0.008
					37625	276.00	276.50	0.50	0.005	-	0.015
					37626	276.50	277.00	0.50	0.005	-	0.007
					37627	277.00	278.10	1.10	0.01	-	0.007
					37628	278.10	279.00	0.90	0.02	-	0.015
278.10	281.10	MF-Bx		flow breccia	37629	279.00	280.00	1.00	0.005	-	0.016
					37630	280.00	281.10	1.10	0.14	-	0.172
					37631	Dup			0.12	-	0.173
					37632	Blank			0.005	-	0.003
281.10	297.00	MF		massive	37633	281.10	282.00	0.90	0.10	0.14	0.050
				292.46 3 cm qv at 50 CA	37634	282.00	283.00	1.00	0.02	-	0.018
297.00	298.20	FP		fine grained; contact at 80 CA							
					37635	291.00	292.00	1.00	0.02	-	0.021
298.20	310.20	MF		fine to medium grained	37636	292.00	292.50	0.50	0.02	-	0.071
					37637	292.50	293.00	0.50	0.02	-	0.016
310.20	314.20	FP		fine to medium grained	37638	293.00	294.00	1.00	0.02	-	0.016
314.20	321.90	MF		massive, dioritic	37639	314.20	315.00	0.80	0.01	-	0.020
					37640	Standard	53Pb		0.61	-	0.540
					37641	315.00	316.00	1.00	0.005	-	0.012
					37642	316.00	317.00	1.00	0.005	-	0.025
					37643	317.00	318.00	1.00	0.02	0.005	0.020
					37644	318.00	319.00	1.00	0.02	-	0.018
					37645	319.00	320.00	1.00	0.01	-	0.012
					37646	320.00	321.00	1.00	0.01	-	0.015
321.90	324.75	FP		as above	37647	321.00	321.90	0.90	0.01	-	0.003
					37648	321.90	322.50	0.60	0.02	-	0.009
					37649	Dup			0.03	-	0.009
					37650	Blank			0.005	-	0.003
					37651	322.50	323.00	0.50	0.05	0.05	0.021
					37652	323.00	324.00	1.00	0.02	-	0.013
					37653	324.00	324.75	0.75	0.15	0.12	0.010
324.75	325.85	MF		massive, dioritic	37654	324.75	325.85	1.10	0.05	-	0.010
					37655	325.85	326.50	0.65	0.005	-	0.012
325.85	328.46	FP		as above	37656	326.50	327.00	0.50	0.005	-	0.006
					37657	327.00	328.00	1.00	0.07	-	0.001
328.46	335.60	MF		massive, dioritic	37658	328.00	328.46	0.46	0.01	-	0.001
					37659	328.46	329.00	0.54	0.03	-	0.006
335.60	336.40	FP		as above	37660	Standard	54Pa		2.81	-	1.500
					37661	329.00	330.00	1.00	0.02	-	0.004

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
					37662	330.00	331.00	1.00	0.08	-	0.010
					37663	331.00	332.00	1.00	0.27	-	0.029
					37664	332.00	333.00	1.00	0.30	0.30	0.042
					37665	333.00	334.00	1.00	0.14	-	0.040
					37666	334.00	335.00	1.00	0.11	-	0.057
					37667	335.00	335.60	0.60	0.10	-	0.094
					37668	335.60	336.40	0.80	0.34	-	0.029
					37669	Dup			0.30	-	0.030
					37670	Blank			0.005	-	0.001
336.40	356.60	MF			37671	336.40	337.00	0.60	0.28	-	0.070
					37672	337.00	338.00	1.00	0.13	-	0.056
					37673	338.00	339.00	1.00	0.09	0.08	0.033
					37674	339.00	340.00	1.00	0.03	-	0.055
					37675	340.00	341.00	1.00	0.005	-	0.015
					37676	341.00	342.00	1.00	1.85	1.71	0.036
					37677	342.00	343.00	1.00	0.02	-	0.031
					37678	343.00	344.00	1.00	0.14	-	0.032
					37679	344.00	345.00	1.00	0.05	-	0.018
					37680	Standard	52Pb		0.34	-	0.336
					37681	345.00	346.00	1.00	0.02	-	0.018
					37682	346.00	347.00	1.00	0.02	-	0.017
					37683	347.00	348.00	1.00	0.03	-	0.012
					37684	348.00	349.00	1.00	0.01	-	0.020
					37685	349.00	350.00	1.00	0.01	-	0.019
					37686	350.00	351.00	1.00	0.01	-	0.016
					37687	351.00	352.00	1.00	0.05	-	0.019
					37688	352.00	353.00	1.00	0.02	-	0.021
					37689	Dup			0.02	-	0.020
					37690	Blank			0.005	-	0.001
					37691	353.00	354.00	1.00	0.02	-	0.016
					37692	354.00	355.00	1.00	0.02	-	0.022
					37693	355.00	356.00	1.00	0.01	0.02	0.024
					37694	356.00	356.60	0.60	0.01	-	0.014
356.60	357.36	FP		as above	37695	356.60	357.36	0.76	0.005	-	0.009
					37696	357.36	358.00	0.64	0.005	-	0.018
					37697	358.00	359.00	1.00	0.12	-	0.016
					37698	359.00	360.00	1.00	0.01	-	0.014
					37699	360.00	361.00	1.00	0.05	-	0.033
					37700	Standard	50Pb		0.85	-	0.730
					37701	361.00	362.00	1.00	0.005	-	0.017
					37702	362.00	363.00	1.00	0.01	-	0.036
					37703	363.00	364.00	1.00	0.02	-	0.015
					37704	364.00	365.00	1.00	0.02	-	0.018

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
					37705	365.00	366.00	1.00	0.07	-	0.017
					37706	366.00	367.00	1.00	0.005	-	0.016
					37707	367.00	368.00	1.00	0.03	-	0.021
					37708	368.00	369.00	1.00	0.02	-	0.016
					37709	Dup			0.005	-	0.016
					37710	Blank			0.005	-	0.010
					37711	369.00	370.00	1.00	0.04	-	0.033
					37712	370.00	371.00	1.00	0.005	-	0.055
					37713	371.00	372.10	1.10	0.005	-	0.043
357.36	372.10	MF		massive, dioritic	37714	372.10	373.00	0.90	0.005	-	0.004
					37715	373.00	374.00	1.00	1.95	2.23	0.456
372.10	373.00	FP		as above	37716	374.00	374.50	0.50	3.91	4.32	0.130
					37717	374.50	375.00	0.50	0.06	-	0.051
373.00	374.50	MF		massive, dioritic, chloritized, 20% po	37718	375.00	376.00	1.00	0.04	-	0.029
					37719	376.00	377.00	1.00	0.01	-	0.008
374.50	378.35	FP		as above: contact at 20 CA	37720	Standard	53Pb		0.58	-	0.540
					37721	377.00	377.50	0.50	0.005	-	0.031
					37722	377.50	378.35	0.85	0.005	-	0.037
378.35	386.70	MF		massive, vesicular	37723	378.35	379.00	0.65	0.03	-	0.084
					37724	379.00	380.00	1.00	0.005	-	0.038
					37725	380.00	381.00	1.00	0.03	-	0.026
					37726	381.00	382.00	1.00	0.005	0.005	0.014
					37727	382.00	383.00	1.00	0.005	-	0.017
					37728	383.00	384.00	1.00	0.02	-	0.018
					37729	Dup			0.005	-	0.018
					37730	Blank			0.005	-	0.005
					37731	384.00	385.00	1.00	0.01	0.005	0.029
					37732	385.00	386.00	1.00	0.01	-	0.016
					37733	386.00	386.70	0.70	0.005	-	0.019
386.70	389.45	FP		as above: fine grained, contact at 20 & 60 CA	37734	386.70	387.50	0.80	0.02	-	0.006
					37735	387.50	388.00	0.50	0.01	-	0.004
					37736	388.00	389.00	1.00	0.02	-	0.013
					37737	389.00	389.45	0.45	0.005	-	0.003
389.45	393.90	MF-Bx			37738	389.45	390.00	0.55	0.005	-	0.061
					37739	390.00	391.00	1.00	0.005	0.005	0.027
					37740	Standard	54Pa		2.67	-	1.490
					37741	391.00	392.00	1.00	0.005	-	0.018
					37742	392.00	393.00	1.00	0.005	-	0.011
					37743	393.00	393.90	0.90	0.005	-	0.014
393.90	395.70	FP		as above:	37744	393.90	394.50	0.60	0.005	-	0.012
					37745	394.50	395.70	1.20	0.01	-	0.033
					37746	395.70	396.50	0.80	0.005	-	0.029
395.70	398.60	FZ		brecciated; sheared at 40 CA	37747	396.50	397.50	1.00	0.005	-	0.083

From	To	Rock Type	Code	Description	Sample#	From	To	Width	Au g/t	Au2 g/t	Cu %
Downhole Tests											
	DDH ID	Depth	AZ	DIP							
	AT-08-09	18	90.2	-43.6							
	AT-08-09	51	91.6	-43.5							
	AT-08-09	102	92.2	-43.3							
	AT-08-09	150	91	-43							
	AT-08-09	201	93.8	-41.9							
	AT-08-09	252	95.6	-40.8							
	AT-08-09	303	99.4	-38.7							
	AT-08-09	351	101.1	-37.2							
	AT-08-09	402	103.6	-35.2							
	AT-08-09	425	104	-34.3							



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

Assay Certificate

8W-0260-RA1Company: **OPAWICA EXPLORATIONS INC.**

Date: APR-11-08

Project:

Attn: F.Sharpley

We hereby certify the following Assay of 74 Core samples submitted FEB-06-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu %
49001	0.08	-	-	0.049
49002	Nil	-	0.2	0.013
49003	0.01	-	0.2	0.030
49004	0.29	-	0.8	0.260
49005	0.02	-	0.9	0.438
49006	0.31	-	0.4	0.162
49007	0.19	-	-	0.033
49008	3.84	4.73	0.3	0.119
49009	0.25	-	0.5	0.155
49010	0.61	-	1.7	0.54
49011	2.55	-	1.5	0.65
49012	0.11	-	0.2	0.026
49013	0.07	-	0.2	0.069
49014	0.16	-	-	0.387
49015	Nil	-	0.1	0.011
49016	0.30	-	1.5	0.454
49017	1.30	2.38	1.7	0.64
49018	0.15	-	0.6	0.216
49019	0.12	-	0.5	0.205
49020	Nil	-	0.1	0.005
49021	0.62	-	1.7	0.70
49022	0.23	-	0.2	0.069
49023	0.03	-	0.1	0.003
49024	2.82	-	0.5	0.235
49025	0.89	-	-	0.309
49026	4.11	-	1.2	0.68
49027	8.09	8.09	1.6	0.88
49028	5.01	-	2.2	1.21
49029	6.00	-	2.0	1.02
49030	2.84	-	4.5	1.48

Certified by Paul Charle



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

Assay Certificate

8W-0260-RA1Company: **OPAWICA EXPLORATIONS INC.**

Date: APR-11-08

Project:

Attn: F.Sharpley

We hereby certify the following Assay of 74 Core samples submitted FEB-06-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu %
49031	8.57	7.61	1.0	0.493
49032	13.44	-	3.4	3.63
49033	14.98	13.30	3.5	1.77
49034	8.81	-	-	1.75
49035	2.71	-	1.3	0.72
49036	3.98	-	1.9	0.94
49037	10.29	-	1.8	0.94
49038	6.03	-	-	1.60
49039	5.31	-	3.2	1.54
49040	0.01	-	0.1	0.008
49041	9.60	-	4.2	1.66
49042	22.29	25.78	-	8.56
49043	1.44	-	2.4	1.05
49044	1.15	-	1.7	0.79
49045	0.12	-	0.1	0.020
49046	0.15	-	0.1	0.013
49047	6.58	-	0.6	0.282
49048	1.91	-	1.4	0.55
49049	1.98	-	0.5	0.216
49050	0.58	-	0.9	0.001
49051	6.79	-	3.2	1.69
49052	7.75	7.68	2.8	1.09
49053	3.05	-	1.2	0.465
49054	0.12	-	0.1	0.022
49055	2.95	-	1.4	0.50
49056	15.77	15.98	-	3.03
49057	0.23	-	0.3	0.048
49058	0.04	-	0.2	0.021
49059	0.01	-	0.2	0.009
49060	Nil	-	0.1	0.002

Certified by Paul Clartie



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

Assay Certificate

8W-0260-RA1Company: **OPAWICA EXPLORATIONS INC.**

Date: APR-11-08

Project:

Attn: F.Sharpley

We hereby certify the following Assay of 74 Core samples
submitted FEB-06-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu %
49061	Nil	-	0.1	0.006
49062	Nil	-	0.1	0.008
49063	Nil	-	0.1	0.003
49064	0.01	-	0.2	0.007
49065	0.02	-	0.1	0.008
49066	0.02	-	0.1	0.006
49067	4.77	5.21	1.4	0.61
49068	5.76	5.07	3.0	1.55
49069	1.60	-	0.4	0.096
49070	0.63	-	1.8	0.55
49071	0.09	-	0.1	0.020
49072	0.07	-	0.2	0.031
49073	27.77	30.86	7.1	4.32
49074	0.80	-	0.7	0.225
Blank	Nil	-	-	-
Std	3.56	-	-	-

Certified by Paul Chattee



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

Assay Certificate

8W-0261-RA1Company: **OPAWICA EXPLORATIONS INC.**

Date: APR-15-08

Project:

Attn: F.Sharpley

We hereby certify the following Assay of 74 Core samples
submitted FEB-06-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu %
49075	0.61	-	0.7	0.334
49076	8.78	4.94	-	1.35
49077	3.43	-	1.6	0.72
49078	0.98	-	1.9	1.03
49079	0.88	-	2.1	1.00
49080	0.01	-	0.1	0.009
49081	17.14	18.51	2.7	1.14
49082	0.36	-	0.2	0.034
49083	0.12	-	0.1	0.028
49084	7.06	4.66	2.5	0.80
49085	1.66	-	3.1	1.27
49086	0.02	-	0.1	0.010
49087	Nil	-	0.2	0.014
49088	0.41	-	2.8	0.085
49089	0.40	-	0.3	0.062
49090	2.88	-	4.7	1.47
49091	0.31	0.48	0.3	0.069
49092	0.69	-	0.8	0.332
49093	3.05	-	1.4	0.64
49094	0.59	-	0.3	0.118
49095	0.06	-	0.1	0.011
49096	0.04	-	0.1	0.016
49097	0.08	-	0.3	0.073
49098	0.12	-	0.4	0.130
49099	0.14	-	0.3	0.155
49100	Nil	-	0.1	0.002
49101	0.39	-	0.3	0.127
49102	0.04	0.03	0.1	0.022
49103	0.09	-	0.2	0.029
49104	0.26	-	0.4	0.240

Certified by Paul Charle



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

Assay Certificate

8W-0261-RA1Company: **OPAWICA EXPLORATIONS INC.**

Date: APR-15-08

Project:

Attn: F.Sharpley

We hereby certify the following Assay of 74 Core samples
submitted FEB-06-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu %
49105	1.83	-	1.0	0.50
49106	0.05	-	0.2	0.018
49107	3.91	5.55	3.0	1.30
49108	1.03	-	1.1	0.51
49109	0.52	-	2.1	1.01
49110	0.57	-	0.9	0.001
49111	0.54	-	0.2	0.028
49112	0.29	-	0.3	0.128
49113	0.12	-	0.4	0.143
49114	Nil	-	0.1	0.009
49115	0.01	-	0.1	0.009
49116	0.20	-	1.2	0.420
49117	0.60	-	1.8	0.68
49118	0.02	-	0.1	0.019
49119	Nil	-	0.1	0.018
49120	Nil	-	0.1	0.002
49121	0.03	-	0.1	0.025
49122	2.47	2.49	0.9	0.178
49123	0.11	-	0.2	0.056
49124	Nil	-	0.3	0.087
49125	0.05	-	0.3	0.029
49126	0.01	-	0.1	0.010
49127	0.02	-	0.2	0.024
49128	0.01	-	0.1	0.011
49129	Nil	-	0.1	0.018
49130	0.60	-	1.7	0.55
49131	0.03	0.01	0.1	0.017
49132	0.02	-	0.2	0.021
49133	0.01	-	0.1	0.018
49134	0.02	-	0.2	0.035

Certified by Paul Charle



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

Assay Certificate

8W-0261-RA1Company: **OPAWICA EXPLORATIONS INC.**

Date: APR-15-08

Project:

Attn: F.Sharpley

We hereby certify the following Assay of 74 Core samples
submitted FEB-06-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu %
49135	0.06	-	0.9	0.152
49136	0.05	-	0.2	0.090
49137	0.01	-	0.1	0.008
49138	1.05	1.41	8.8	0.035
49139	2.57	2.43	9.6	0.027
49140	0.02	-	0.1	0.002
49141	0.29	-	4.0	0.007
49142	0.03	-	1.0	0.089
49143	0.05	-	0.6	0.123
49144	0.10	-	0.5	0.086
49145	0.45	-	0.8	0.135
49146	1.92	-	2.3	0.088
49147	0.08	-	0.8	0.162
49148	3.50	3.70	2.3	0.61
Blank	0.01	-	-	-
Std	3.56	-	-	-

Certified by Paul Chactie



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

Assay Certificate

8W-0262-RA1

Company: **OPAWICA EXPLORATIONS INC.**

Date: APR-15-08

Project:

Attn: F.Sharpley

We hereby certify the following Assay of 74 Core samples
submitted FEB-06-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu %
49149	0.28	0.18	0.7	0.178
49150	2.72	-	4.8	1.45
49151	0.01	-	0.1	0.002
49152	0.07	0.34	0.3	0.040
49153	0.01	-	0.2	0.027
49154	0.13	-	0.9	0.304
49155	0.05	-	0.7	0.227
49156	0.11	-	2.2	0.59
49157	0.03	-	0.4	0.110
49158	Nil	-	0.1	0.013
49159	Nil	-	0.1	0.022
49160	Nil	-	0.1	0.001
49161	Nil	-	0.2	0.039
49162	Nil	-	0.1	0.020
49163	Nil	-	0.1	0.008
49164	Nil	-	0.1	0.003
49165	Nil	-	0.1	0.007
49166	Nil	-	0.1	0.005
49167	0.14	0.16	1.4	0.153
49168	Nil	-	0.6	0.108
49169	Nil	-	0.2	0.029
49170	0.58	-	0.8	0.001
49171	Nil	-	0.1	0.015
49172	0.24	-	1.2	0.225
49173	Nil	-	0.1	0.001
49174	Nil	-	0.1	0.001
49175	0.01	-	0.1	0.010
49176	Nil	Nil	0.1	0.006
49177	Nil	-	0.1	0.009
49178	Nil	-	0.2	0.006

Certified by Paul Christie



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

Assay Certificate

8W-0262-RA1Company: **OPAWICA EXPLORATIONS INC.**

Date: APR-15-08

Project:

Attn: F.Sharpley

We hereby certify the following Assay of 74 Core samples
submitted FEB-06-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu %
49179	0.01	-	0.1	0.007
49180	Nil	-	0.1	0.001
49181	Nil	-	0.1	0.012
49182	0.01	-	0.8	0.144
49183	Nil	-	0.6	0.158
49184	0.03	-	0.5	0.129
49185	Nil	-	0.1	0.007
49186	0.01	Nil	0.1	0.016
49187	0.01	-	0.1	0.020
49188	0.24	-	3.9	0.471
49189	0.06	-	1.3	0.257
49190	0.63	-	1.7	0.55
49191	0.41	-	1.1	0.436
49192	Nil	-	0.1	0.004
49193	0.11	-	1.0	0.336
49194	0.07	-	0.3	0.080
49195	0.50	0.57	4.7	1.53
49196	Nil	-	0.1	0.032
49197	0.38	-	4.7	1.47
49198	Nil	-	0.1	0.003
49199	0.01	-	0.1	0.002
49200	Nil	-	0.1	0.001
49201	Nil	-	0.2	0.017
49202	0.03	-	0.7	0.071
49203	0.11	-	1.0	0.304
49204	0.08	-	0.4	0.118
49205	0.07	-	0.6	0.122
49206	0.15	-	1.2	0.255
49207	0.05	0.02	0.3	0.046
49208	Nil	-	0.1	0.005

Certified by Paul Chaitre



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

Assay Certificate

8W-0262-RA1

Company: **OPAWICA EXPLORATIONS INC.**

Date: APR-15-08

Project:

Attn: F.Sharpley

We hereby certify the following Assay of 74 Core samples
submitted FEB-06-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu %
49209	0.08	-	0.9	0.250
49210	2.71	-	4.9	1.47
49211	0.28	-	5.3	1.29
49212	0.09	-	1.0	0.237
49213	0.03	-	0.9	0.082
49214	Nil	-	0.2	0.014
49215	0.01	-	0.3	0.036
49216	Nil	-	0.7	0.008
49217	Nil	-	0.3	0.008
49218	0.04	-	0.8	0.134
49219	0.04	-	1.0	0.133
49220	Nil	-	0.1	0.001
49221	Nil	-	0.1	0.001
49222	Nil	Nil	0.1	0.004
Blank	Nil	-	-	-
Std	3.61	-	-	-

Certified by Paul Chastre



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Assay Certificate

8W-0263-RA1

Company: Opawica Explorations

Date: APR-11-08

Project:

Attn: F.Sharpley

We hereby certify the following Assay of 14 Core samples submitted FEB-06-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Ag g/tonne	Cu %
49223	Nil	-	0.1	0.002
49224	Nil	-	0.1	0.001
49225	0.35	0.48	3.9	1.16
49226	0.02	-	0.1	0.009
49227	0.57	0.41	4.5	1.25
49228	0.09	-	1.7	0.446
49229	Nil	-	0.4	0.050
49230	0.60	-	0.9	0.002
49231	Nil	-	0.1	0.008
49232	0.02	-	0.4	0.074
37367	0.01	-	-	0.001
37368	Nil	-	-	0.001
37369	0.02	-	-	0.001
37370	Nil	-	-	0.001
Blank	Nil	-	-	-
Std	3.48	-	-	-

Certified by Denis Chastre



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

8W-0285-RA1

Assay Certificate

Company: Opawica Explorations

Date: APR-09-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 33 Core samples submitted FEB-08-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49233	Nil	-	0.012
49234	0.14	-	0.079
49235	0.24	0.24	0.041
49236	0.04	-	0.021
49237	0.02	-	0.008
49238	0.22	-	0.032
49239	0.05	-	0.020
49240	0.20	-	0.067
49241	Nil	-	0.010
49242	0.60	-	0.55
49243	0.08	-	0.076
49244	0.02	-	0.031
49245	0.05	-	0.047
49246	Nil	-	0.018
49247	0.10	-	0.058
49248	0.01	-	0.026
49249	0.57	-	0.001
49250	0.55	0.62	0.139
49251	Nil	-	0.121
49252	0.04	-	0.087
49253	0.08	-	0.065
49254	0.09	-	0.033
49255	0.21	-	0.053
49256	0.08	-	0.054
49257	Nil	-	0.001
49258	0.14	-	0.041
49259	0.02	-	0.012
49260	0.01	-	0.010
49261	0.01	-	0.014
49262	0.01	Nil	0.008

Certified by Denis Chastey



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

8W-0285-RA1

Company: **Opawica Explorations**

Date: APR-09-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 33 Core samples submitted FEB-08-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49263	0.01	-	0.024
49264	0.01	-	0.021
49265	Nil	-	0.025
Blank	Nil	-	-
STD OxK48	3.53	-	-

Certified by Denis Chant



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

8W-0297-RA1

Company: **Opawica**

Date: APR-09-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 40 Core samples submitted FEB-11-08 by .

Sample Number	Au PPM	Au Check PPM	Cu %
49266	0.23	-	0.033
49267	0.40	-	0.097
49268	0.24	-	0.009
49269	0.61	-	0.52
49270	0.58	0.49	0.018
49271	0.18	-	0.008
49272	0.37	-	0.014
49273	0.29	-	0.010
49274	0.28	-	0.009
49275	0.53	-	0.011
49276	0.17	-	0.010
49277	1.49	-	0.022
49278	1.77	-	0.025
49279	0.01	-	0.001
49280	0.09	-	0.019
49281	0.26	-	0.024
49282	0.09	-	0.016
49283	Nil	-	0.010
49284	0.04	-	0.070
49285	4.83	5.93	0.017
49286	0.01	-	0.012
49287	0.02	-	0.021
49288	0.05	-	0.015
49289	2.83	-	1.46
49290	0.97	0.97	0.013
49291	0.37	-	0.011
49292	0.04	-	0.022
49293	0.05	-	0.028
49294	0.21	-	0.009
49295	0.29	-	0.009

Certified by Denis Sharpley



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

8W-0297-RA1

Company: **Opawica**

Date: APR-09-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 40 Core samples
submitted FEB-11-08 by .

Sample Number	Au PPM	Au Check PPM	Cu %
49296	0.03	-	0.003
49297	1.09	0.95	0.015
49298	0.76	-	0.011
49299	0.83	-	0.017
49300	0.01	-	0.011
49301	0.58	-	0.001
49302	0.05	-	0.005
49303	Nil	-	0.011
49304	0.77	0.83	0.062
49305	0.23	0.34	0.066
Blank	Nil	-	-
STD OxK48	3.49	-	-

Certified by Dennis Christie



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

8W-0298-RA1Company: **Opawica**

Date: APR-09-08

Project:

Attn: F.Sharpley

We hereby certify the following Assay of 38 Core samples
submitted FEB-11-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49306	Nil	-	0.002
49307	0.34	-	0.095
49308	0.01	-	0.009
49309	0.67	0.52	0.123
49310	0.01	-	0.003
49311	0.09	-	0.024
49312	0.15	-	0.025
49313	0.03	-	0.025
49314	0.07	-	0.015
49315	0.04	-	0.015
49316	0.65	-	0.54
49317	0.02	-	0.013
49318	Nil	-	0.005
49319	Nil	-	0.003
49320	Nil	-	0.008
49321	0.38	0.59	0.014
49322	0.22	-	0.015
49323	0.20	-	0.021
49324	2.88	-	1.48
49325	0.59	0.45	0.038
49326	0.65	-	0.034
49327	0.04	-	0.012
49328	0.20	-	0.039
49329	0.12	-	0.037
49330	Nil	-	0.020
49331	0.02	-	0.012
49332	0.02	-	0.007
49333	0.16	-	0.074
49334	1.29	-	0.155
49335	0.01	-	0.016

Certified by Paul Christie



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

8W-0298-RA1

Company: **Opawica**

Date: APR-09-08

Project:

Attn: F.Sharpley

We hereby certify the following Assay of 38 Core samples submitted FEB-11-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49336	0.18	-	0.144
49337	0.56	-	0.041
49338	0.09	-	0.066
49339	0.56	0.51	0.125
49340	0.63	-	0.001
49341	0.07	-	0.014
49342	0.03	-	0.031
49343	0.04	-	0.046
Blank	0.01	-	-
STD OxK48	3.60	-	-

Certified by Paul Christie



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

Assay Certificate

8W-0350-RA1

Company: **Opawica Explorations**

Date: APR-04-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 60 Core samples submitted FEB-15-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49344	nil	-	0.055
49345	0.19	0.20	0.120
49346	0.02	-	0.028
49347	0.01	-	0.006
49348	0.02	-	0.008
49349	nil	-	0.003
49350	nil	-	0.004
49351	0.01	-	0.024
49352	0.01	-	0.018
49353	0.62	-	0.54
49354	0.02	-	0.002
49355	nil	-	0.009
49356	nil	-	0.003
49357	0.01	-	0.028
49358	0.01	-	0.006
49359	0.09	-	0.093
49360	0.03	-	0.033
49361	0.07	0.05	0.026
49362	0.07	-	0.029
49363	0.01	-	0.001
49364	0.09	-	0.011
49365	0.01	-	0.006
49366	0.04	-	0.112
49367	0.01	-	0.009
49368	0.02	-	0.034
49369	0.04	-	0.047
49370	0.05	0.05	0.074
49371	0.02	-	0.007
49372	0.04	-	0.005
49373	2.86	-	1.48

Certified by Denis Chantre



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

Assay Certificate

8W-0350-RA1

Company: **Opawica Explorations**

Date: APR-04-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 60 Core samples submitted FEB-15-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49374	0.02	-	0.002
49375	0.01	-	0.007
49376	0.02	-	0.003
49377	0.02	-	0.019
49378	0.01	-	0.005
49379	0.02	-	0.009
49380	0.02	0.01	0.001
49381	0.02	-	0.004
49382	0.02	-	0.001
49383	nil	-	0.002
49384	0.02	-	0.016
49385	0.02	-	0.008
49386	0.02	-	0.012
49387	0.01	-	0.008
49388	0.01	-	0.018
49389	nil	-	0.003
49390	0.02	0.03	0.009
49391	0.02	-	0.026
49392	0.60	-	0.001
49393	0.01	-	0.004
49394	0.04	-	0.002
49395	0.01	-	0.010
49396	0.02	-	0.016
49397	0.03	-	0.030
49398	0.05	-	0.067
49399	0.35	0.30	0.056
49400	0.04	-	0.037
49401	0.03	-	0.039
49402	nil	-	0.001
49403	0.06	-	0.165

Certified by Denis Chata



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

Assay Certificate

8W-0350-RA1

Company: **Opawica Explorations**

Date: APR-04-08

Project:

Attn: F. Sharpley

*We hereby certify the following Assay of 60 Core samples
submitted FEB-15-08 by .*

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
Blank	nil	-	-
STD OxK48	3.51	-	-

Certified by Denis Chantre



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

Assay Certificate

8W-0351-RA1Company: **Opawica Explorations**

Date: APR-04-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 60 Core samples
submitted FEB-15-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49404	0.15	-	0.261
49405	0.03	-	0.042
49406	Nil	-	0.056
49407	0.05	-	0.079
49408	0.04	-	0.055
49409	0.04	-	0.050
49410	0.12	0.13	0.271
49411	0.01	-	0.016
49412	0.62	-	0.54
49413	0.01	-	0.013
49414	0.01	-	0.018
49415	Nil	-	0.001
49416	0.03	-	0.043
49417	Nil	-	0.040
49418	0.09	-	0.020
49419	0.18	-	0.62
49420	0.13	0.13	0.177
49421	0.12	-	0.168
49422	Nil	-	0.002
49423	0.21	-	0.325
49424	0.26	0.23	0.264
49425	0.06	-	0.085
49426	0.06	-	0.080
49427	0.10	0.13	0.086
49428	Nil	-	0.004
49429	0.01	-	0.008
49430	Nil	-	0.004
49431	0.01	-	0.010
49432	2.78	-	1.49
49433	Nil	-	0.011

Certified by Paul Christie



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

Assay Certificate

8W-0351-RA1Company: **Opawica Explorations**

Date: APR-04-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 60 Core samples
submitted FEB-15-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49434	0.01	-	0.010
49435	Nil	-	0.001
49436	Nil	-	0.001
49437	0.01	-	0.008
49438	Nil	0.01	0.001
49439	Nil	-	0.001
49440	Nil	-	0.001
49441	Nil	-	0.002
49442	Nil	-	0.001
49443	Nil	-	0.001
49444	Nil	-	0.001
49445	0.01	-	0.001
49446	0.01	Nil	0.001
49447	Nil	-	0.001
49448	Nil	-	0.001
49449	Nil	-	0.001
49450	Nil	-	0.001
49451	0.01	-	0.003
49452	0.58	-	0.001
49453	0.01	-	0.011
49454	Nil	-	0.006
49455	Nil	-	0.004
49456	0.01	-	0.004
49457	Nil	Nil	0.001
49458	0.01	-	0.001
49459	Nil	-	0.001
49460	Nil	-	0.001
49461	0.01	-	0.001
49462	Nil	-	0.001
49463	Nil	-	0.001

Certified by Paul Charle



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

Assay Certificate

8W-0351-RA1

Company: **Opawica Explorations**

Date: APR-04-08

Project:

Attn: F. Sharpley

*We hereby certify the following Assay of 60 Core samples
submitted FEB-15-08 by .*

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
Blank	Nil	-	-
STD OxK48	3.48	-	-

Certified by Paul Chastre



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

Assay Certificate

8W-0352-RA1

Company: Opawica Explorations

Date: APR-09-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 60 Core samples submitted FEB-15-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49464	nil	-	0.002
49465	nil	-	0.001
49466	nil	-	0.005
49467	nil	-	0.008
49468	nil	-	0.005
49469	nil	0.01	0.005
49470	nil	-	0.009
49471	nil	-	0.009
49472	0.57	-	0.55
49473	nil	-	0.005
49474	nil	-	0.006
49475	nil	-	0.007
49476	nil	-	0.010
49477	nil	-	0.007
49478	nil	-	0.008
49479	nil	-	0.018
49480	0.03	-	0.034
49481	0.02	0.04	0.035
49482	nil	-	0.002
49483	0.04	-	0.029
49484	nil	-	0.008
49485	nil	-	0.003
49486	0.03	-	0.029
49487	0.03	-	0.027
49488	0.04	-	0.040
49489	nil	-	0.028
49490	nil	-	0.028
49491	0.01	-	0.007
49492	2.85	-	1.49
49493	0.01	nil	0.002

Certified by Denis Chotie



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

8W-0352-RA1

Assay Certificate

Company: **Opawica Explorations**

Date: APR-09-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 60 Core samples submitted FEB-15-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49494	nil	-	0.009
49495	0.01	-	0.012
49496	0.02	0.01	0.009
49497	nil	-	0.010
49498	nil	-	0.008
49499	0.01	-	0.010
49500	nil	-	0.002
49501	nil	-	0.002
49502	nil	-	0.001
49503	nil	-	0.004
49504	0.01	-	0.008
49505	0.03	-	0.022
49506	nil	-	0.006
49507	0.02	-	0.027
49508	nil	-	0.002
49509	nil	-	0.022
49510	0.01	nil	0.016
49511	nil	-	0.039
49512	0.32	-	0.337
49513	0.01	-	0.014
49514	0.02	-	0.017
49515	0.06	-	0.054
49516	0.15	-	0.105
49517	0.02	-	0.021
49518	0.04	-	0.020
49519	0.05	0.06	0.033
49520	nil	-	0.008
49521	nil	-	0.007
49522	nil	-	0.001
49523	0.01	-	0.008

Certified by Dennis Clinton



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

Assay Certificate

8W-0352-RA1

Company: **Opawica Explorations**

Date: APR-09-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 60 Core samples
submitted FEB-15-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
Blank	nil	-	-
STD OxK48	3.49	-	-

Certified by Denis Chantre



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

Assay Certificate

8W-0353-RA1Company: **Opawica Explorations**

Date: APR-04-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 60 Core samples submitted FEB-15-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49524	nil	-	0.001
49525	nil	-	0.001
49526	nil	-	0.014
49527	nil	-	0.010
49528	0.11	-	0.141
49529	0.10	0.10	0.099
49530	0.02	-	0.016
49531	0.01	-	0.006
49532	0.61	-	0.55
49533	0.02	-	0.012
49534	nil	-	0.005
49535	0.02	-	0.015
49536	nil	-	0.008
49537	0.04	-	0.045
49538	0.35	-	0.315
49539	0.65	0.39	0.68
49540	0.20	-	0.084
49541	0.37	-	0.073
49542	0.01	-	0.003
49543	nil	-	0.008
49544	nil	-	0.002
49545	nil	-	0.004
49546	nil	-	0.010
49547	nil	-	0.001
49548	0.13	0.16	0.078
49549	0.01	-	0.002
49550	nil	-	0.001
49551	nil	-	0.001
49552	2.81	-	1.49
49553	nil	-	0.006

Certified by Denis Sharpley



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

Assay Certificate

8W-0353-RA1Company: **Opawica Explorations**

Date: APR-04-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 60 Core samples submitted FEB-15-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49554	0.02	-	0.004
49555	nil	-	0.003
49556	nil	-	0.006
49557	0.01	-	0.006
49558	nil	-	0.006
49559	0.01	nil	0.005
49560	0.01	-	0.005
49561	0.01	-	0.005
49562	0.01	-	0.001
49563	0.01	-	0.004
49564	0.01	-	0.001
49565	0.01	-	0.001
49566	0.01	-	0.001
49567	0.02	-	0.004
49568	0.01	-	0.012
49569	0.01	-	0.002
49570	0.13	-	0.004
49571	0.01	-	0.002
49572	0.32	-	0.336
49573	0.01	-	0.001
49574	nil	-	0.001
49575	0.01	-	0.001
49576	0.01	-	0.001
49577	nil	-	0.001
49578	nil	-	0.001
49579	0.01	0.02	0.002
49580	nil	-	0.001
49581	nil	-	0.001
49582	nil	-	0.007
49583	nil	-	0.001

Certified by Denis Sharpley



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

Assay Certificate

8W-0353-RA1

Company: **Opawica Explorations**

Date: APR-04-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 60 Core samples submitted FEB-15-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
Blank	nil	-	-
STD OxK48	3.56	-	-

Certified by Denis Chants



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

Assay Certificate

8W-0366-RA1Company: **Opawica Explorations Inc.**

Date: APR-04-08

Project:

Attn:

We hereby certify the following Assay of 61 Core samples submitted FEB-19-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49584	0.01	-	0.001
49585	0.01	-	0.001
49586	nil	-	0.001
49587	0.02	-	0.003
49588	0.07	-	0.012
49589	0.02	-	0.005
49590	nil	-	0.001
49591	0.01	-	0.001
49592	0.61	-	0.55
49593	0.01	-	0.001
49594	nil	-	0.001
49595	nil	nil	0.001
49596	nil	-	0.001
49597	nil	-	0.001
49598	0.01	-	0.003
49599	0.01	-	0.001
49600	0.01	-	0.001
49601	nil	-	0.001
49602	nil	-	0.001
49603	nil	-	0.001
49604	nil	0.01	0.001
49605	nil	-	0.001
49606	0.01	-	0.001
49607	nil	-	0.002
49608	0.01	-	0.014
49609	0.02	-	0.041
49610	0.03	-	0.051
49611	0.14	0.15	0.239
49612	2.85	-	1.49
49613	0.09	-	0.174

Certified by Doris Chanty



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

Assay Certificate

8W-0366-RA1Company: **Opawica Explorations Inc.**

Date: APR-04-08

Project:

Attn:

We hereby certify the following Assay of 61 Core samples submitted FEB-19-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49614	0.09	-	0.002
49615	0.04	-	0.065
49616	0.07	-	0.013
49617	2.61	1.71	0.008
49618	0.03	-	0.002
49619	0.23	-	0.014
49620	0.02	-	0.007
49621	0.02	-	0.008
49622	nil	-	0.001
49623	0.02	-	0.016
49624	0.01	-	0.019
49625	nil	-	0.005
49626	0.04	-	0.066
49627	0.01	-	0.009
49628	0.62	0.24	0.008
49629	0.10	-	0.004
49630	nil	-	0.002
49631	nil	-	0.002
49632	0.32	-	0.336
49633	0.02	0.02	0.004
49634	0.02	-	0.012
49635	0.06	-	0.063
49636	0.07	-	0.034
49637	0.08	-	0.028
49638	0.07	-	0.039
49639	0.48	-	0.116
49640	0.31	-	0.137
49641	0.24	-	0.133
49642	0.01	-	0.002
49643	0.14	-	0.136

Certified by Dennis Shantz



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

Assay Certificate

8W-0366-RA1

Company: **Opawica Explorations Inc.**

Date: APR-04-08

Project:

Attn:

We hereby certify the following Assay of 61 Core samples submitted FEB-19-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49644	0.02	-	0.014
Blank	nil	-	-
STD OxK48	3.60	-	-

Certified by Denis Chodro



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

Assay Certificate

8W-0367-RA1Company: **Opawica Explorations Inc.**Date: **FEB-28-08**

Project:

Attn:

We hereby certify the following Assay of 61 Core samples submitted FEB-19-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49645	0.09	-	0.061
49646	0.12	-	0.074
49647	0.08	-	0.041
49648	0.47	-	0.329
49649	0.52	0.60	0.315
49650	0.05	-	0.032
49651	0.23	-	0.234
49652	0.62	-	0.54
49653	0.15	-	0.223
49654	0.25	-	0.221
49655	0.16	-	0.253
49656	0.09	-	0.174
49657	0.09	-	0.162
49658	0.16	-	0.098
49659	0.13	-	0.216
49660	0.13	0.08	0.168
49661	0.10	-	0.166
49662	0.01	-	0.001
49663	0.98	-	0.446
49664	0.08	-	0.067
49665	0.11	-	0.084
49666	0.10	-	0.113
49667	0.12	-	0.226
49668	0.11	-	0.195
49669	0.30	-	0.187
49670	0.12	0.13	0.132
49671	0.13	-	0.157
49672	2.85	-	1.49
49673	0.19	-	0.196
49674	0.06	-	0.083

Certified by Denis chad



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

Assay Certificate

8W-0367-RA1

Company: **Opawica Explorations Inc.**

Date: FEB-28-08

Project:

Attn:

We hereby certify the following Assay of 61 Core samples submitted FEB-19-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49675	nil	-	0.051
49676	nil	-	0.023
49677	nil	-	0.034
49678	0.15	0.16	0.022
49679	nil	-	0.011
49680	0.01	-	0.019
49681	0.01	-	0.021
49682	nil	-	0.001
49683	nil	-	0.026
49684	0.02	-	0.023
49685	nil	-	0.034
49686	0.03	0.03	0.043
49687	0.03	-	0.039
49688	0.12	-	0.043
49689	nil	-	0.018
49690	0.02	-	0.021
49691	nil	-	0.018
49692	0.32	-	0.335
49693	nil	-	0.006
49694	0.03	-	0.031
49695	0.06	-	0.094
49696	0.08	-	0.093
49697	0.08	0.07	0.087
49698	0.12	-	0.094
49699	0.06	-	0.061
49700	0.09	-	0.054
49701	0.07	-	0.056
49702	nil	-	0.001
49703	0.09	-	0.063
49704	0.11	-	0.062

Certified by Denis Chantre



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

Assay Certificate

8W-0367-RA1

Company: **Opawica Explorations Inc.**

Date: **FEB-28-08**

Project:

Attn:

We hereby certify the following Assay of 61 Core samples submitted FEB-19-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49705	0.07	0.08	0.061
Blank	nil	-	-
STD OxK48	3.53	-	-

Certified by Denis Chantre



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

8W-0368-RA1

Company: **Opawica Explorations Inc.**

Date: FEB-27-08

Project:

Attn:

We hereby certify the following Assay of 48 Core samples submitted FEB-19-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49706	0.02	-	0.057
49707	0.06	-	0.057
49708	0.04	-	0.051
49709	0.07	0.04	0.058
49710	0.05	-	0.050
49711	0.08	-	0.063
49712	0.60	-	0.55
49713	0.16	-	0.101
49714	0.04	-	0.067
49715	0.05	-	0.063
49716	0.05	-	0.069
49717	0.01	-	0.090
49718	0.15	0.20	0.120
49719	0.05	-	0.068
49720	0.05	-	0.070
49721	0.05	-	0.075
49722	0.01	-	0.002
49723	0.07	-	0.076
49724	0.04	-	0.061
49725	0.14	-	0.060
49726	0.03	-	0.063
49727	0.06	-	0.074
49728	0.05	-	0.085
49729	0.09	-	0.105
49730	0.10	-	0.076
49731	0.07	-	0.086
49732	2.89	-	1.48
49733	0.40	0.48	0.195
49734	0.03	-	0.061
49735	0.07	-	0.069

Certified by Denis Chatoe



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

8W-0368-RA1Company: **Opawica Explorations Inc.**

Date: FEB-27-08

Project:

Attn:

We hereby certify the following Assay of 48 Core samples submitted FEB-19-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49736	0.16	-	0.130
49737	0.15	-	0.117
49738	0.16	-	0.126
49739	0.11	0.09	0.125
49740	0.09	-	0.134
49741	0.08	-	0.126
49742	nil	-	0.002
49743	0.09	-	0.177
49744	0.12	-	0.171
49745	0.15	-	0.265
49746	0.21	-	0.202
49747	0.36	0.45	0.277
49748	0.14	-	0.128
49749	0.03	-	0.074
49750	1.45	1.33	0.054
49751	0.05	-	0.054
49752	0.32	-	0.334
49753	0.04	-	0.045
Blank	0.01	-	-
STD OxK48	3.59	-	-

Certified by



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

8W-0448-RA1

Company: Opawica Exploration Inc.

Date: APR-04-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 50 Core samples submitted FEB-29-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49754	0.04	-	0.069
49755	0.43	-	0.051
49756	11.73	14.40	0.022
49757	0.06	-	0.022
49758	0.18	-	0.143
49759	0.14	0.25	0.132
49760	0.35	-	0.149
49761	0.44	-	0.151
49762	0.01	-	0.002
49763	0.09	-	0.156
49764	0.24	-	0.226
49765	0.19	-	0.195
49766	0.32	-	0.336
49767	0.15	-	0.165
49768	0.34	-	0.010
49769	0.04	-	0.014
49770	0.08	0.08	0.010
49771	0.07	-	0.032
49772	0.62	-	0.54
49773	0.05	-	0.027
49774	0.02	-	0.018
49775	Nil	-	0.012
49776	0.06	-	0.056
49777	Nil	-	0.012
49778	0.09	-	0.092
49779	2.37	-	0.51
49780	4.15	4.05	0.343
49781	1.32	-	0.014
49782	0.62	-	0.54
49783	Nil	-	0.009

Certified by Denis Choty



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

8W-0448-RA1

Company: **Opawica Exploration Inc.**

Date: APR-04-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 50 Core samples
submitted FEB-29-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49784	0.32	-	0.249
49785	0.50	-	0.475
49786	0.17	-	0.191
49787	0.02	-	0.018
49788	0.16	-	0.152
49789	0.28	-	0.219
49790	0.18	-	0.173
49791	0.15	-	0.161
49792	0.01	-	0.004
49793	0.25	0.22	0.241
49794	0.13	-	0.196
49795	0.16	-	0.267
49796	0.16	-	0.170
49797	0.07	-	0.089
49798	0.11	-	0.108
49799	0.09	-	0.109
49800	0.02	-	0.042
49801	Nil	-	0.009
49802	2.81	-	1.49
49803	Nil	-	0.007
Blank	Nil	-	-
STD OXJ 64	2.33	-	-

Certified by Denis Chantre



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

8W-0449-RA1Company: **Opawica Exploration Inc.**

Date: APR-04-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 53 Core samples submitted FEB-29-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49804	0.01	-	0.002
49805	Nil	-	0.003
49806	Nil	-	0.004
49807	Nil	-	0.005
49808	Nil	-	0.004
49809	0.23	0.22	0.253
49810	0.16	-	0.187
49811	0.15	-	0.194
49812	0.01	-	0.004
49813	0.10	-	0.135
49814	0.05	-	0.058
49815	0.14	-	0.184
49816	0.13	-	0.051
49817	0.03	-	0.027
49818	0.03	-	0.030
49819	0.08	-	0.055
49820	0.08	-	0.054
49821	0.10	0.11	0.088
49822	0.31	-	0.337
49823	0.08	-	0.069
49824	0.02	-	0.017
49825	0.04	-	0.039
49826	0.02	-	0.075
49827	0.07	-	0.181
49828	0.12	-	0.256
49829	0.07	-	0.167
49830	0.01	-	0.011
49831	Nil	-	0.010
49832	Nil	-	0.005
49833	0.07	0.10	0.322

Certified by Paul Chartre



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

8W-0449-RA1Company: **Opawica Exploration Inc.**

Date: APR-04-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 53 Core samples submitted FEB-29-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49834	0.01	-	0.009
49835	0.06	-	0.093
49836	0.06	-	0.089
49837	0.01	-	0.006
49838	0.63	-	0.55
49839	Nil	-	0.005
49840	0.01	-	0.008
49841	0.02	-	0.030
49842	Nil	-	0.046
49843	Nil	-	0.009
49844	Nil	-	0.009
49845	0.03	-	0.030
49846	0.02	-	0.011
49847	0.03	-	0.009
49848	Nil	-	0.002
49849	0.03	-	0.015
49850	0.01	-	0.007
49851	0.04	-	0.017
49852	0.10	0.10	0.069
49853	Nil	-	0.002
49854	0.02	-	0.001
49855	0.08	-	0.002
49856	0.03	-	0.008
BLANK	Nil	-	-
STD OXJ 64	2.25	-	-

Certified by Paul Charle



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

Assay Certificate

8W-0458-RA1Company: **Opawica Exploration Inc.**

Date: APR-04-08

Project:

Attn: F.Sharpley

We hereby certify the following Assay of 64 Core samples submitted MAR-02-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49857	0.02	-	0.035
49858	Nil	-	0.004
49859	Nil	-	0.001
49860	Nil	-	0.002
49861	Nil	-	0.002
49862	Nil	Nil	0.009
49863	Nil	-	0.003
49864	Nil	-	0.001
49865	Nil	-	0.003
49866	0.63	-	0.55
49867	Nil	-	0.005
49868	Nil	-	0.001
49869	Nil	-	0.005
49870	Nil	-	0.006
49871	0.01	-	0.018
49872	Nil	-	0.027
49873	0.02	-	0.033
49874	0.02	-	0.032
49875	Nil	-	0.001
49876	0.01	-	0.033
49877	Nil	-	0.006
49878	Nil	Nil	0.003
49879	Nil	-	0.004
49880	Nil	-	0.002
49881	Nil	-	0.002
49882	Nil	-	0.001
49883	Nil	-	0.006
49884	Nil	-	0.002
49885	2.85	-	1.49
49886	Nil	-	0.001

Certified by Paul Christie



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

Assay Certificate

8W-0458-RA1Company: **Opawica Exploration Inc.**

Date: APR-04-08

Project:

Attn: F.Sharpley

We hereby certify the following Assay of 64 Core samples submitted MAR-02-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49887	Nil	-	0.004
49888	Nil	-	0.003
49889	Nil	-	0.003
49890	Nil	-	0.002
49891	Nil	-	0.002
49892	Nil	-	0.003
49893	Nil	-	0.001
49894	Nil	-	0.001
49895	Nil	-	0.001
49896	0.09	0.07	0.081
49897	0.07	-	0.066
49898	0.05	-	0.063
49899	0.09	-	0.070
49900	0.10	-	0.044
49901	0.03	-	0.037
49902	0.04	-	0.058
49903	0.33	-	0.335
49904	0.08	-	0.060
49905	0.01	-	0.060
49906	Nil	-	0.006
49907	0.01	-	0.025
49908	Nil	Nil	0.001
49909	Nil	-	0.001
49910	Nil	-	0.005
49911	Nil	-	0.004
49912	Nil	-	0.001
49913	1.13	1.24	0.065
49914	0.08	-	0.028
49915	Nil	-	0.010
49916	0.20	-	0.008

Certified by Paul Chartie



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

Assay Certificate

8W-0458-RA1

Company: **Opawica Exploration Inc.**

Date: APR-04-08

Project:

Attn: F.Sharpley

We hereby certify the following Assay of 64 Core samples submitted MAR-02-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49917	0.02	-	0.010
49918	0.34	0.18	0.024
49919	0.44	-	0.029
49920	0.17	-	0.043
Blank	Nil	-	-
STD OXJ 64	2.29	-	-

Certified by Paul Chartre



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

Assay Certificate

8W-0459-RA1Company: **Opawica Exploration Inc.**

Date: APR-03-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 66 Core samples submitted MAR-02-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49921	0.37	-	0.051
49922	0.61	-	0.54
49923	0.24	-	0.024
49924	0.19	0.23	0.017
49925	3.77	3.63	0.058
49926	0.31	-	0.041
49927	0.25	-	0.030
49928	0.31	-	0.042
49929	0.21	-	0.048
49930	0.89	-	0.044
49931	0.89	-	0.044
49932	0.01	-	0.001
49933	0.04	-	0.035
49934	0.02	-	0.018
49935	0.02	-	0.004
49936	Nil	-	0.007
49937	0.13	0.06	0.016
49938	0.01	-	0.011
49939	0.01	-	0.008
49940	0.02	-	0.032
49941	0.03	-	0.036
49942	2.88	-	1.49
49943	0.01	-	0.006
49944	0.08	-	0.020
49945	0.08	-	0.013
49946	0.13	-	0.037
49947	0.10	-	0.029
49948	0.08	0.09	0.029
49949	0.09	-	0.025
49950	0.03	-	0.022

Certified by Paul Chaitre



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

Assay Certificate

8W-0459-RA1

Company: **Opawica Exploration Inc.**

Date: APR-03-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 66 Core samples submitted MAR-02-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49951	0.04	-	0.025
49952	Nil	-	0.003
49953	0.06	-	0.030
49954	0.01	-	0.023
49955	0.01	-	0.015
49956	0.53	-	0.034
49957	0.04	-	0.030
49958	0.03	-	0.027
49959	0.08	-	0.055
49960	0.03	0.03	0.093
49961	0.04	-	0.140
49962	0.30	-	0.337
49963	0.11	-	0.085
49964	0.16	-	0.116
49965	0.02	-	0.019
49966	0.04	-	0.014
49967	0.30	-	0.069
49968	0.16	-	0.106
49969	2.54	2.47	0.225
49970	1.68	-	0.086
49971	1.37	-	0.084
49972	0.01	-	0.004
49973	0.08	-	0.011
49974	0.09	-	0.008
49975	3.05	3.29	0.258
49976	0.21	-	0.110
49977	0.07	-	0.084
49978	0.10	-	0.031
49979	0.15	-	0.021
49980	0.01	-	0.005

Certified by Paul Chartrie



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

Assay Certificate

8W-0459-RA1

Company: **Opawica Exploration Inc.**

Date: APR-03-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 66 Core samples submitted MAR-02-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49981	0.33	-	0.038
49982	0.60	-	0.54
49983	0.03	-	0.042
49984	0.01	0.01	0.002
49985	0.04	-	0.077
49986	0.12	-	0.082
Blank	Nil	-	-
STD OXJ 64	2.43	-	-

Certified by Paul Chaitre



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

8W-0477-RA1

Company: **Opawica Exploration Inc.**

Date: APR-03-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 41 Core samples
submitted MAR-04-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
49987	0.05	-	0.085
49988	Nil	-	0.009
49989	Nil	-	0.010
49990	Nil	-	0.009
49991	Nil	-	0.009
49992	Nil	-	0.001
49993	Nil	-	0.010
49994	Nil	-	0.011
49995	Nil	-	0.038
49996	0.07	0.07	0.070
49997	Nil	-	0.216
49998	0.02	-	0.137
49999	0.11	0.17	0.155
50000	0.02	-	0.086
50001	Nil	-	0.014
50002	0.31	-	0.337
50003	Nil	-	0.024
50004	Nil	-	0.010
50005	Nil	Nil	0.008
50006	Nil	-	0.006
50007	Nil	-	0.004
50008	Nil	-	0.001
50009	Nil	-	0.010
50010	Nil	-	0.011
50011	0.01	-	0.012
50012	Nil	-	0.001
50013	0.01	-	0.050
50014	Nil	Nil	0.007
50015	Nil	-	0.002
50016	Nil	-	0.008

Certified by Denis Sharpley



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

8W-0477-RA1

Company: **Opawica Exploration Inc.**

Date: APR-03-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 41 Core samples submitted MAR-04-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
50017	Nil	-	0.027
50018	0.14	0.14	0.171
50019	0.26	0.29	0.207
50020	0.02	-	0.130
50021	0.02	-	0.072
50022	0.63	-	0.55
50023	0.14	-	0.053
50024	0.01	-	0.053
50025	Nil	-	0.004
50026	0.01	-	0.035
50027	Nil	-	0.065
BLANK	Nil	-	-
STD OXJ 64	2.36	-	-

Certified by Denis Sharpley



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

8W-0478-RA1

Company: Opawica Exploration Inc.

Date: APR-01-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 49 Core samples submitted MAR-04-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
50028	0.03	0.04	0.039
50029	0.01	-	0.065
50030	0.01	-	0.044
50031	0.02	-	0.042
50032	0.01	-	0.002
50033	0.01	-	0.016
50034	Ni 1	-	0.004
50035	Ni 1	-	0.004
50036	Ni 1	-	0.054
50037	0.01	-	0.054
50038	Ni 1	-	0.074
50039	0.01	0.01	0.112
50040	Ni 1	-	0.073
50041	2.86	-	1.49
50042	Ni 1	-	0.033
50043	Ni 1	-	0.034
50044	0.01	-	0.046
50045	0.01	-	0.042
50046	0.02	-	0.054
50047	Ni 1	-	0.042
50048	Ni 1	-	0.048
50049	Ni 1	-	0.037
50050	0.01	-	0.039
50051	Ni 1	-	0.003
50052	0.03	-	0.086
50053	0.01	Ni 1	0.075
50054	0.01	-	0.046
50055	Ni 1	-	0.037
50056	Ni 1	-	0.034
50057	0.01	-	0.063

Certified by Denis Christie



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

8W-0478-RA1

Assay Certificate

Company: Opawica Exploration Inc.

Date: APR-01-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 49 Core samples
submitted MAR-04-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
50058	0.02	-	0.054
50059	0.31	-	0.335
50060	0.02	-	0.061
50061	0.11	-	0.120
50062	0.06	-	0.052
50063	0.01	-	0.047
50064	0.02	0.02	0.056
50065	Ni1	-	0.131
50066	0.16	-	0.126
50067	0.02	-	0.062
50068	Ni1	-	0.063
50069	Ni1	-	0.002
50070	0.02	-	0.103
50071	0.09	0.09	0.101
50072	0.02	-	0.023
50073	0.01	-	0.034
50074	0.01	-	0.019
50075	0.01	-	0.028
50076	0.01	-	0.026
BLANK	Ni1	-	-
STD OXJ 64	2.51	-	-

Certified by Dennis Chantler



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

8W-0544-RA1

Company: **Opawica Exploration Inc.**

Date: MAR-31-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 43 Core samples submitted MAR-08-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu PFM	Cu %
50067 Missing	-	-	-	-
50068 Missing	-	-	-	-
50069 Missing	-	-	-	-
50070 Missing	-	-	-	-
50071 Missing	-	-	-	-
50072 Missing	-	-	-	-
50073 Missing	-	-	-	-
50074 Missing	-	-	-	-
50075 Missing	-	-	-	-
50076 Missing	-	-	-	-
50077	0.03	-	269	0.027
50078	0.01	-	23	0.003
50079	0.61	-	5450	0.55
50080	0.01	-	39	0.004
50081	0.02	-	367	0.037
50082	0.01	-	313	0.031
50083	0.03	-	599	0.060
50084	Ni 1	-	49	0.005
50085	Ni 1	-	115	0.012
50086	0.03	-	229	0.023
50087	0.01	-	109	0.011
50088	0.01	0.01	109	0.011
50089	Ni 1	-	13	0.001
50090	0.01	-	455	0.046
50091	0.04	-	1420	0.142
50092	0.01	-	299	0.030
50093	0.01	-	273	0.027
50094	Ni 1	0.01	111	0.011
50095	0.04	-	75	0.008
50096	Ni 1	-	73	0.007

Certified by Denis Sharpley



Established 1928

Swastika Laboratories Ltd.

Assaying - Consulting - Representation

Page 2 of 2

8W-0544-RA1

Assay Certificate

Company: **Opawica Exploration Inc.**

Date: MAR-31-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 43 Core samples submitted MAR-08-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu PPM	Cu %
50097	Nil	-	83	0.008
50098	0.02	0.01	109	0.011
50099	2.85	-	>10000	1.48
50100	Nil	-	35	0.004
50101	0.02	-	129	0.013
50102	0.02	-	213	0.021
50103	0.01	-	89	0.009
50104	Nil	-	27	0.003
50105	Nil	-	69	0.007
50106	0.03	-	155	0.016
50107	0.02	0.03	223	0.023
50108	0.02	-	219	0.022
50109	Nil	-	15	0.002
50110	Nil	-	221	0.022
50111	0.01	-	51	0.005
50112	Nil	-	35	0.004
50113	Nil	Nil	41	0.004
50114	0.02	-	65	0.007
50115	Nil	-	279	0.028
50116	Nil	-	129	0.013
50117	Nil	-	31	0.003
50118	0.33	-	3370	0.337
50119	Nil	-	91	0.009
BLANK	Nil	-	-	-
STD OXJ 64	2.43	-	-	-

Certified by Denis Chantre



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

8W-0545-RA1

Company: **Opawica Exploration Inc.**

Date: APR-01-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 57 Core samples submitted MAR-08-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
50120	Nil	-	0.010
50121	0.01	-	0.042
50122	Nil	-	0.008
50123	0.01	-	0.021
50124	0.01	-	0.016
50125	0.02	-	0.010
50126	0.20	-	0.017
50127	0.12	-	0.018
50128	0.01	-	0.002
50129	Nil	-	0.015
50130	0.07	-	0.089
50131	1.18	-	0.039
50132	0.06	-	0.019
50133	0.19	-	0.083
50134	4.70	5.35	0.159
50135	0.97	-	0.195
50136	0.23	-	0.033
50137	0.81	-	0.129
50138	0.62	-	0.54
50139	7.75	5.83	0.477
50140	0.04	-	0.066
50141	0.02	-	0.011
50142	0.02	-	0.132
50143	0.07	-	0.110
50144	0.03	-	0.216
50145	0.01	-	0.066
50146	0.01	-	0.014
50147	0.01	-	0.014
50148	Nil	-	0.002
50149	Nil	-	0.018

Certified by Denis Chantre



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

8W-0545-RA1

Company: Opawica Exploration Inc.

Date: APR-01-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 57 Core samples submitted MAR-08-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
50150	Nil	-	0.007
50151	0.06	-	0.026
50152	0.01	-	0.006
50153	0.68	0.58	0.59
50154	0.16	-	0.025
50155	0.02	-	0.022
50156	0.01	-	0.006
50157	Nil	-	0.005
50158	2.88	-	1.49
50159	0.01	-	0.003
50160	0.05	-	0.005
50161	0.01	-	0.006
50162	Nil	Nil	0.008
50163	0.01	-	0.048
50164	Nil	-	0.036
50165	0.02	-	0.026
50166	Nil	-	0.059
50167	Nil	-	0.055
50168	Nil	-	0.002
50169	0.01	-	0.065
50170	0.01	-	0.085
50171	Nil	-	0.037
50172	Nil	-	0.045
50173	Nil	0.01	0.004
50174	Nil	-	0.004
50175	0.11	-	0.51
50176	Nil	-	0.008
BLANK	Nil	-	-
STD OXJ 64	2.45	-	-

Certified by Denis Chant



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

8W-0598-RA1

Company: **Opawica Explorations Inc.**

Date: MAR-28-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 50 core samples submitted MAR-12-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
50177	0.32	-	0.337
50178	0.08	-	0.031
50179	0.08	-	0.062
50180	0.10	-	0.126
50181	0.05	-	0.055
50182	2.30	2.23	0.052
50183	0.04	-	0.016
50184	Nil	-	0.017
50185	0.03	-	0.023
50186	0.03	-	0.023
50187	Nil	-	0.002
50188	0.03	-	0.016
50189	Nil	-	0.005
50190	Nil	-	0.011
50191	0.01	-	0.008
50192	0.02	-	0.015
50193	0.03	-	0.042
50194	0.13	-	0.139
50195	0.03	-	0.036
50196	0.62	-	0.55
50197	0.14	-	0.064
50198	0.13	-	0.066
50199	0.55	-	0.283
50200	0.36	-	0.336
50201	0.69	0.82	0.82
50202	0.19	0.16	0.207
50203	0.19	-	0.139
50204	0.34	-	0.206
50205	0.21	-	0.191
50206	Nil	-	0.004

Certified by Denis Chant



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

8W-0598-RA1

Company: **Opawica Explorations Inc.**

Date: MAR-28-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 50 core samples submitted MAR-12-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
50207	0.15	-	0.127
50208	0.12	-	0.181
50209	0.82	0.70	0.331
50210	0.41	-	0.52
50211	0.66	-	0.448
50212	0.08	-	0.052
50213	0.07	-	0.050
50214	0.10	0.11	0.062
50215	0.12	-	0.080
50216	2.85	-	1.48
50217	0.03	-	0.046
50218	0.01	-	0.005
50219	0.08	-	0.027
50220	0.16	-	0.033
50221	0.26	-	0.092
50222	0.11	-	0.071
50223	0.22	-	0.112
50224	0.22	-	0.158
50225	0.17	-	0.157
50226	Ni1	-	0.005
Blank	Ni1	-	-
STD OxJ64	2.28	-	-

Certified by Denis Chantler



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

8W-0599-RA1

Company: **Opawica Explorations Inc.**

Date: MAR-28-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 50 core samples submitted MAR-12-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
50227	0.35	-	0.51
50228	0.06	-	0.086
50229	0.02	-	0.030
50230	Nil	-	0.006
50231	Nil	0.01	0.007
50232	0.01	-	0.012
50233	Nil	-	0.007
50234	0.01	-	0.013
50235	0.02	-	0.008
50236	0.32	-	0.334
50237	0.08	-	0.061
50238	0.13	-	0.066
50239	0.06	-	0.029
50240	0.10	-	0.031
50241	0.10	-	0.027
50242	0.69	0.67	0.187
50243	0.19	-	0.091
50244	0.38	0.55	0.097
50245	0.97	-	0.090
50246	0.01	-	0.009
50247	0.02	-	0.005
50248	0.01	-	0.004
50249	0.38	-	0.159
50250	0.40	-	0.090
50251	0.07	0.05	0.095
50252	0.02	-	0.043
50253	0.01	-	0.018
50254	Nil	-	0.012
50255	0.14	-	0.143
50256	0.62	-	0.55

Certified by Denis Sharpley



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

8W-0599-RA1

Assay Certificate

Company: Opawica Explorations Inc.

Date: MAR-28-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 50 core samples submitted MAR-12-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
50257	0.28	0.22	0.68
50258	0.06	-	0.264
50259	0.05	-	0.141
50260	Ni 1	-	0.037
50261	0.04	-	0.041
50262	Ni 1	-	0.009
50263	0.01	-	0.013
50264	0.01	-	0.040
50265	0.01	-	0.044
50266	Ni 1	-	0.002
50267	0.01	-	0.020
50268	0.01	-	0.004
50269	Ni 1	-	0.011
50270	Ni 1	-	0.026
50271	0.01	-	0.006
50272	0.01	0.01	0.013
50273	0.01	-	0.022
50274	Ni 1	-	0.045
50275	Ni 1	-	0.013
50276	2.88	-	1.49
Blank	Ni 1	-	-
STD OxJ64	2.32	-	-

Certified by Denis Chantre



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

Assay Certificate

8W-0615-RA1Company: **Opawica Explorations Inc.**

Date: MAR-28-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 60 core samples
submitted MAR-14-08 by F. sharpley.

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
50277	0.01	-	0.007
50278	0.05	-	0.047
50279	0.13	0.09	0.056
50280	0.02	-	0.027
50281	0.04	-	0.073
50282	0.03	-	0.082
50283	0.02	-	0.040
50284	0.01	-	0.090
50285	Ni 1	-	0.080
50286	0.01	-	0.001
50287	0.01	-	0.051
50288	Ni 1	0.01	0.029
50289	0.01	-	0.030
50290	0.02	-	0.051
50291	0.01	-	0.040
50292	0.06	-	0.036
50293	Ni 1	-	0.060
50294	0.04	-	0.048
50295	0.04	-	0.082
50296	0.82	-	0.73
50297	0.10	-	0.072
50298	0.66	-	0.239
50299	0.02	-	0.078
50300	0.04	-	0.062
50301	0.14	-	0.108
50302	0.05	-	0.163
50303	4.01	4.39	0.374
50304	1.71	1.68	0.147
50305	2.40	-	0.155
50306	0.01	-	0.002

Certified by Dennis Chanty



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

Assay Certificate

8W-0615-RA1Company: **Opawica Explorations Inc.**

Date: MAR-28-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 60 core samples submitted MAR-14-08 by F. sharpley.

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
50307	0.01	-	0.032
50308	0.01	-	0.036
50309	Ni 1	0.02	0.056
50310	Ni 1	-	0.004
50311	0.01	-	0.014
50312	Ni 1	-	0.015
50313	0.02	-	0.054
50314	Ni 1	-	0.030
50315	Ni 1	-	0.007
50316	2.88	-	1.49
50317	0.05	-	0.083
50318	0.02	-	0.021
50319	0.02	-	0.049
50320	0.03	-	0.031
50321	0.01	-	0.011
50322	0.06	0.08	0.047
50323	Ni 1	-	0.043
50324	0.01	-	0.019
50325	Ni 1	-	0.021
50326	Ni 1	-	0.001
50327	Ni 1	-	0.005
50328	Ni 1	-	0.003
50329	Ni 1	-	0.003
50330	Ni 1	-	0.003
50331	Ni 1	-	0.003
50332	Ni 1	-	0.004
50333	Ni 1	-	0.007
50334	Ni 1	-	0.017
50335	0.21	0.26	0.061
50336	0.33	-	0.334

Certified by Denis Charty



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

8W-0615-RA1

Assay Certificate

Company: **Opawica Explorations Inc.**

Date: MAR-28-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 60 core samples submitted MAR-14-08 by F. sharpley.

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
Blank	Nil	-	-
STD OxJ64	2.49	-	-

Certified by Denis Chahs



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

Assay Certificate

8W-0616-RA1

Company: **Opawica Explorations Inc.**

Date: MAR-28-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 60 Core samples
submitted MAR-14-08 by F. Sharpley.

Sample Number	Au g / tonne	Au Check g / tonne	Cu %
50337	0.03	-	0.043
50338	Ni l	Ni l	0.012
50339	Ni l	-	0.012
50340	0.04	-	0.010
50341	0.02	-	0.014
50342	0.04	-	0.014
50343	0.07	-	0.005
50344	0.01	-	0.010
50345	0.01	-	0.010
50346	Ni l	-	0.001
50347	Ni l	-	0.005
50348	0.01	-	0.006
50349	0.01	-	0.007
50350	Ni l	-	0.004
50351	Ni l	-	0.010
50352	0.01	-	0.006
50353	0.02	-	0.067
50354	0.02	-	0.017
50355	0.49	0.50	0.090
50356	0.61	-	0.54
50357	0.02	-	0.013
50358	0.01	-	0.016
50359	0.03	-	0.046
50360	Ni l	-	0.010
50361	0.11	-	0.011
50362	0.05	-	0.013
50363	0.14	-	0.025
50364	0.12	-	0.026
50365	0.01	-	0.002
50366	0.27	0.26	0.196

Certified by Dennis Chantre



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

Assay Certificate

8W-0616-RA1

Company: **Opawica Explorations Inc.**

Date: MAR-28-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 60 Core samples
submitted MAR-14-08 by F. Sharpley.

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
50367	0.22	0.20	0.170
50368	0.07	-	0.110
50369	2.88	-	1.48
50370	0.04	-	0.110
50371	0.01	-	0.002
50372	0.05	-	0.064
50373	0.34	0.57	0.009
50374	0.05	-	0.045
50375	0.10	-	0.015
50376	0.10	-	0.019
50377	0.10	-	0.017
50378	0.01	-	0.001
50379	0.04	-	0.021
50380	0.08	-	0.029
50381	0.03	-	0.031
50382	0.01	-	0.032
50383	0.02	-	0.039
50384	0.06	-	0.062
50385	0.37	-	0.310
50386	0.21	-	0.170
50387	0.29	-	0.336
50388	0.10	-	0.110
50389	Ni1	-	0.046
50390	0.33	-	0.080
50391	0.42	0.41	0.120
50392	0.27	-	0.080
50393	0.24	-	0.090
50394	0.11	-	0.226
50395	0.01	-	0.005
50396	0.02	-	0.004

Certified by Denis Chrahan



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

8W-0616-RA1

Assay Certificate

Company: **Opawica Explorations Inc.**

Date: MAR-28-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 60 Core samples
submitted MAR-14-08 by F. Sharpley.

Sample

Number

Au Au Check
g/tonne g/tonne

Cu
%

Blank Nil - -
STD OxJ64 2.21 - -

Certified by Denis Chantre



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

Assay Certificate

8W-0619-RA1

Company: **OPAWICA EXPLORATION INC.**

Date: MAR-28-08

Project:

Attn: F. SHARPLEY

We hereby certify the following Assay of 60 CORE samples submitted MAR-17-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
50397	0.01	-	0.001
50398	0.04	-	0.033
50399	Ni 1	-	0.009
50400	0.02	-	0.016
50401	0.01	-	0.009
50402	0.01	-	0.011
50403	Ni 1	-	0.009
50404	0.01	0.01	0.015
50405	0.01	-	0.014
50406	0.01	-	0.008
50407	2.81	-	1.49
50408	Ni 1	-	0.007
50409	Ni 1	-	0.023
50410	0.01	-	0.020
50411	0.01	0.02	0.022
50412	0.01	-	0.014
50413	Ni 1	-	0.015
50414	0.01	-	0.005
50415	0.01	-	0.012
50416	0.01	-	0.012
50417	Ni 1	-	0.001
50418	Ni 1	-	0.010
50419	0.01	-	0.008
50420	0.01	-	0.009
50421	0.01	-	0.009
50422	0.02	0.01	0.022
50423	0.01	-	0.003
50424	0.02	-	0.012
50425	0.01	-	0.012
50426	0.01	-	0.007

Certified by Denis Chantre



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

8W-0619-RA1

Assay Certificate

Company: OPAWICA EXPLORATION INC.

Date: MAR-28-08

Project:

Attn: F. SHARPLEY

We hereby certify the following Assay of 60 CORE samples submitted MAR-17-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
50427	2.85	-	1.50
50428	0.01	-	0.010
50429	0.01	-	0.016
50430	0.01	-	0.039
50431	0.02	-	0.136
50432	0.01	-	0.093
50433	0.01	-	0.002
50434	Nil	-	0.002
50435	Nil	-	0.039
50436	0.02	-	0.044
50437	Nil	-	0.001
50438	Nil	-	0.030
50439	Nil	-	0.001
50440	Nil	-	0.006
50441	Nil	-	0.006
50442	Nil	-	0.008
50443	Nil	-	0.007
50444	Nil	-	0.010
50445	Nil	-	0.011
50446	0.02	0.01	0.009
50447	0.30	-	0.337
50448	Nil	-	0.007
50449	Nil	-	0.017
50450	Nil	-	0.011
50451	Nil	-	0.018
50452	0.01	-	0.010
50453	Nil	-	0.010
50454	Nil	-	0.013
50455	0.02	0.02	0.010
50456	Nil	-	0.010

Certified by Dennis Sharpley



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

8W-0619-RA1

Company: **OPAWICA EXPLORATION INC.**

Date: MAR-28-08

Project:

Attn: F. SHARPLEY

We hereby certify the following Assay of 60 CORE samples submitted MAR-17-08 by .

Sample Number	Au g /tonne	Au Check g /tonne	Cu %
BLANK	Nil	-	-
STD OXJ 64	2.35	-	-

Certified by Dennis Chotka



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

8W-0620-RA1

Company: OPAWICA EXPLORATION INC.

Date: MAR-28-08

Project:

Attn: F. SHARPLEY

We hereby certify the following Assay of 40 CORE samples submitted MAR-17-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
50457	Ni 1	-	0.001
50458	0.01	-	0.009
50459	0.01	-	0.010
50460	Ni 1	-	0.005
50461	0.01	Ni 1	0.007
50462	0.02	-	0.057
50463	Ni 1	-	0.016
50464	Ni 1	-	0.022
50465	Ni 1	-	0.021
50466	0.86	-	0.73
50467	Ni 1	-	0.023
50468	Ni 1	-	0.046
50469	0.01	0.03	0.056
50470	Ni 1	-	0.015
50471	Ni 1	-	0.034
50472	Ni 1	-	0.039
50473	Ni 1	-	0.033
50474	0.07	0.09	0.048
50475	Ni 1	-	0.050
50476	Ni 1	-	0.001
50477	Ni 1	-	0.003
50478	Ni 1	-	0.010
50479	Ni 1	-	0.003
50480	Ni 1	-	0.014
50481	Ni 1	-	0.014
50482	Ni 1	-	0.012
50483	Ni 1	-	0.008
50484	Ni 1	-	0.011
50485	Ni 1	-	0.007
50486	0.64	-	0.54

Certified by Denis Chant



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

8W-0620-RA1

Company: OPAWICA EXPLORATION INC.

Date: MAR-28-08

Project:

Attn: F. SHARPLEY

We hereby certify the following Assay of 40 CORE samples submitted MAR-17-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
50487	Nil	-	0.006
50488	Nil	-	0.006
50489	Nil	-	0.002
50490	Nil	-	0.014
50491	Nil	-	0.007
50492	0.06	0.04	0.011
50493	Nil	-	0.010
50494	Nil	-	0.011
50495	Nil	-	0.011
50496	Nil	-	0.001
BLANK STD OXJ 64	Nil	-	-
	2.36	-	-

Certified by Denis Charley



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

8W-0667-RA1

Company: Opawica Explorations Inc.

Date: MAR-31-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 30 Core samples submitted MAR-14-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
50497	0.03	-	0.014
50498	0.01	-	0.006
50499	0.01	-	0.010
50500	Ni 1	-	0.009
37501	0.01	0.01	0.012
37502	Ni 1	-	0.011
37503	0.01	-	0.013
37504	0.01	-	0.017
37505	2.78	-	1.49
37506	Ni 1	-	0.019
37507	Ni 1	-	0.054
37508	0.02	-	0.025
37509	Ni 1	-	0.069
37510	0.16	-	0.152
37511	0.22	0.15	0.172
37512	0.01	-	0.020
37513	0.01	-	0.026
37514	0.02	-	0.024
37515	Ni 1	-	0.001
37516	Ni 1	-	0.012
37517	0.02	-	0.005
37518	Ni 1	-	0.032
37519	Ni 1	-	0.003
37520	Ni 1	-	0.016
37521	Ni 1	-	0.340
37522	0.09	0.05	0.058
37523	0.02	-	0.011
37524	0.31	-	0.337
37525	Ni 1	-	0.040
37526	0.01	-	0.015

Certified by Denis Chantre



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

8W-0667-RA1

Company: **Opawica Explorations Inc.**

Date: MAR-31-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 30 Core samples submitted MAR-14-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
BLANK	Ni 1	-	-
STD OXJ 64	2.31	-	-

Certified by Denis Chantay



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

8W-0668-RA1Company: **Opawica Explorations Inc.**

Date: MAR-31-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 45 Core samples
submitted MAR-14-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
37527	0.01	-	0.012
37528	0.01	-	0.024
37529	0.03	-	0.025
37530	Nil	-	0.020
37531	0.14	-	0.020
37532	0.01	-	0.015
37533	Nil	-	0.014
37534	Nil	-	0.002
37535	Nil	-	0.004
37536	Nil	-	0.026
37537	0.01	0.01	0.009
37538	0.03	-	0.019
37539	Nil	-	0.005
37540	Nil	-	0.007
37541	0.02	-	0.028
37542	0.01	-	0.055
37543	Nil	-	0.012
37544	0.85	-	0.73
37545	Nil	-	0.036
37546	Nil	-	0.016
37547	Nil	-	0.015
37548	Nil	Nil	0.011
37549	Nil	-	0.012
37550	0.02	-	0.009
37551	Nil	-	0.012
37552	Nil	-	0.010
37553	Nil	-	0.009
37554	Nil	-	0.001
37555	Nil	-	0.009
37556	Nil	-	0.009

Certified by Dennis Sharpley



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

8W-0668-RA1

Company: Opawica Explorations Inc.

Date: MAR-31-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 45 Core samples submitted MAR-14-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
37557	Nil	-	0.009
37558	Nil	-	0.009
37559	Nil	-	0.019
37560	Nil	-	0.040
37561	Nil	Nil	0.022
37562	Nil	-	0.013
37563	Nil	-	0.014
37564	0.64	-	0.54
37565	Nil	-	0.014
37566	Nil	-	0.008
37567	0.05	0.07	0.023
37568	Nil	-	0.003
37569	Nil	-	0.005
37570	Nil	-	0.003
37571	Nil	-	0.009
BLANK	Nil	-	-
STD OXJ 64	2.54	-	-

Certified by Dennis Sharpley



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Assay Certificate

8W-0669-RA1Company: **Opawica Explorations Inc.**

Date: APR-03-08

Project:

Attn: F. Sharpley

We hereby certify the following Assay of 25 Core samples submitted MAR-14-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
37572	0.01	-	0.053
37573	0.02	-	0.057
37574	0.02	-	0.001
37575	0.01	-	0.014
37576	0.05	-	0.016
37577	0.01	-	0.020
37578	Nil	-	0.013
37579	0.04	-	0.019
37580	0.03	-	0.018
37581	Nil	-	0.013
37582	0.03	0.03	0.011
37583	2.88	-	1.48
37584	0.01	-	0.015
37585	0.05	-	0.013
37586	0.01	-	0.017
37587	Nil	-	0.006
37588	Nil	-	0.014
37589	0.01	-	0.016
37590	0.01	-	0.017
37591	0.01	-	0.018
37592	Nil	-	0.002
37593	Nil	-	0.016
37594	0.02	-	0.018
37595	Nil	-	0.016
37596	0.03	-	0.012
Blank	Nil	-	-
Standard OxJ 64	2.30	-	-

Certified by



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 3

8W-0715-RA1

Assay Certificate

Company: OPAWICA EXPLORATION INC.

Date: APR-07-08

Project:

Attn: F. SHARPLEY

We hereby certify the following Assay of 60 CORE samples submitted MAR-26-08 by .

Sample Number	Au g/tonne	Au CHECK g/tonne	Cu %
37597	0.02	-	0.012
37598	0.02	-	0.012
37599	0.04	0.07	0.010
37600	Nil	-	0.010
37601	0.02	-	0.011
37602	0.32	-	0.338
37603	0.05	-	0.013
37604	Nil	-	0.011
37605	Nil	-	0.019
37606	Nil	-	0.025
37607	Nil	-	0.016
37608	0.02	-	0.011
37609	0.02	-	0.016
37610	0.04	0.03	0.014
37611	0.02	-	0.014
37612	0.01	-	0.002
37613	0.02	-	0.007
37614	0.01	-	0.014
37615	0.01	-	0.009
37616	Nil	-	0.010
37617	0.01	-	0.004
37618	Nil	-	0.011
37619	Nil	-	0.007
37620	Nil	-	0.003
37621	0.08	-	0.030
37622	0.84	-	0.73
37623	0.05	-	0.018
37624	0.01	-	0.008
37625	Nil	-	0.015
37626	Nil	-	0.007

Certified by Denis Chantre



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 3

Assay Certificate

8W-0715-RA1

Company: **OPAWICA EXPLORATION INC.**

Date: APR-07-08

Project:

Attn: F. SHARPLEY

We hereby certify the following Assay of 60 CORE samples submitted MAR-26-08 by .

Sample Number	Au g/tonne	Au CHECK g/tonne	Cu %
37627	0.01	-	0.007
37628	0.02	-	0.015
37629	Nil	-	0.016
37630	0.14	-	0.172
37631	0.12	-	0.173
37632	Nil	-	0.003
37633	0.10	0.14	0.050
37634	0.02	-	0.018
37635	0.02	-	0.021
37636	0.02	-	0.071
37637	0.02	-	0.016
37638	0.02	-	0.016
37639	0.01	-	0.020
37640	0.61	-	0.54
37641	Nil	-	0.012
37642	Nil	-	0.025
37643	0.02	Nil	0.020
37644	0.02	-	0.018
37645	0.01	-	0.012
37646	0.01	-	0.015
37647	0.01	-	0.003
37648	0.02	-	0.009
37649	0.03	-	0.009
37650	Nil	-	0.003
37651	0.05	0.05	0.021
37652	0.02	-	0.013
37653	0.15	0.12	0.010
37654	0.05	-	0.010
37655	Nil	-	0.012
37656	Nil	-	0.006

Certified by Denis Chanty



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 3 of 3

Assay Certificate

8W-0715-RA1

Company: OPAWICA EXPLORATION INC.

Date: APR-07-08

Project:

Attn: F. SHARPLEY

We hereby certify the following Assay of 60 CORE samples submitted MAR-26-08 by .

Sample Number	Au g/tonne	Au CHECK g/tonne	Cu %
BLANK	0.01	-	-
STD OXJ 64	2.30	-	-

Certified by Dennis Choty



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

8W-0716-RA1

Company: OPAWICA EXPLORATION INC.

Date: APR-02-08

Project:

Attn: F. SHARPLEY

We hereby certify the following Assay of 40 CORE samples submitted MAR-26-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
37657	0.07	-	0.001
37658	0.01	-	0.001
37659	0.03	-	0.006
37660	2.81	-	1.50
37661	0.02	-	0.004
37662	0.08	-	0.010
37663	0.27	-	0.029
37664	0.30	0.30	0.042
37665	0.14	-	0.040
37666	0.11	-	0.057
37667	0.10	-	0.094
37668	0.34	-	0.029
37669	0.30	-	0.030
37670	Nil	-	0.001
37671	0.28	-	0.070
37672	0.13	-	0.056
37673	0.09	0.08	0.033
37674	0.03	-	0.055
37675	Nil	-	0.015
37676	1.85	1.71	0.036
37677	0.02	-	0.031
37678	0.14	-	0.032
37679	0.05	-	0.018
37680	0.34	-	0.336
37681	0.02	-	0.018
37682	0.02	-	0.017
37683	0.03	-	0.012
37684	0.01	-	0.020
37685	0.01	-	0.019
37686	0.01	-	0.016

Certified by Denis Sharpley



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

8W-0716-RA1

Company: **OPAWICA EXPLORATION INC.**

Date: APR-02-08

Project:

Attn: F. SHARPLEY

We hereby certify the following Assay of 40 CORE samples submitted MAR-26-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
37687	0.05	-	0.019
37688	0.02	-	0.021
37689	0.02	-	0.020
37690	Nil	-	0.001
37691	0.02	-	0.016
37692	0.02	-	0.022
37693	0.01	0.02	0.024
37694	0.01	-	0.014
37695	Nil	-	0.009
37696	Nil	-	0.018
BLANK	Nil	-	-
STD OXJ 64	2.47	-	-

Certified by Dennis Sharpley



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

8W-0717-RA1Company: **OPAWICA EXPLORATION INC.**

Date: APR-03-08

Project:

Attn: **F. SHARPLEY**

We hereby certify the following Assay of 54 CORE samples submitted MAR-26-08 by .

Sample Number	Au g/tonne	Au CHECK g/tonne	Cu %
37697	0.12	-	0.016
37698	0.01	-	0.014
37699	0.05	-	0.033
37700	0.85	-	0.73
37701	Nil	-	0.017
37702	0.01	-	0.036
37703	0.02	-	0.015
37704	0.02	-	0.018
37705	0.07	-	0.017
37706	Nil	-	0.016
37707	0.03	-	0.021
37708	0.02	-	0.016
37709	Nil	-	0.016
37710	Nil	-	0.01
37711	0.04	-	0.033
37712	Nil	-	0.055
37713	Nil	-	0.043
37714	Nil	-	0.004
37715	1.95	2.23	0.456
37716	3.91	4.32	0.130
37717	0.06	-	0.051
37718	0.04	-	0.029
37719	0.01	-	0.008
37720	0.58	-	0.54
37721	Nil	-	0.031
37722	Nil	-	0.037
37723	0.03	-	0.084
37724	Nil	-	0.038
37725	0.03	-	0.026
37726	Nil	Nil	0.014

Certified by Denis Sharpley



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

8W-0717-RA1

Company: **OPAWICA EXPLORATION INC.**

Date: APR-03-08

Project:

Attn: **F. SHARPLEY**

We hereby certify the following Assay of 54 CORE samples submitted MAR-26-08 by .

Sample Number	Au g/tonne	Au CHECK g/tonne	Cu %
37727	Nil	-	0.017
37728	0.02	-	0.018
37729	Nil	-	0.018
37730	Nil	-	0.005
37731	0.01	Nil	0.029
37732	0.01	-	0.016
37733	Nil	-	0.019
37734	0.02	-	0.006
37735	0.01	-	0.004
37736	0.02	-	0.013
37737	Nil	-	0.003
37738	Nil	-	0.061
37739	Nil	Nil	0.027
37740	2.67	-	1.49
37741	Nil	-	0.018
37742	Nil	-	0.011
37743	Nil	-	0.014
37744	Nil	-	0.012
37745	0.01	-	0.033
37746	Nil	-	0.029
37747	Nil	-	0.083
37748	Nil	-	0.035
37749	Nil	-	0.033
37750	Nil	-	0.001
BLANK	Nil	-	-
STD OXJ 64	2.34	-	-

Certified by



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 1 of 2

Assay Certificate

8W-0718-RA1Company: **OPAWICA EXPLORATION INC.**

Date: APR-03-08

Project:

Attn: **F. SHARPLEY**

We hereby certify the following Assay of 40 CORE samples submitted MAR-26-08 by .

Sample Number	Au g/tonne	Au Check g/tonne	Cu %
50501	Nil	-	0.010
50502	Nil	-	0.009
50503	Nil	-	0.009
50504	Nil	-	0.011
50505	Nil	-	0.011
50506	Nil	Nil	0.009
50507	Nil	-	0.010
50508	Nil	-	0.006
50509	Nil	-	0.006
50510	0.32	-	0.335
50511	Nil	-	0.017
50512	Nil	-	0.094
50513	Nil	-	0.005
50514	Nil	-	0.012
50515	Nil	-	0.004
50516	Nil	Nil	0.010
50517	Nil	-	0.011
50518	Nil	-	0.008
50519	Nil	-	0.009
50520	Nil	-	0.001
50521	Nil	-	0.009
50522	Nil	-	0.013
50523	0.13	-	0.010
50524	Nil	-	0.010
50525	Nil	-	0.006
50526	Nil	0.01	0.012
50527	Nil	-	0.008
50528	0.01	-	0.011
50529	Nil	-	0.009
50530	0.83	-	0.72

Certified by D. Sharpley



Established 1928

Swastika Laboratories Ltd

Assaying - Consulting - Representation

Page 2 of 2

Assay Certificate

8W-0718-RA1

Company: **OPAWICA EXPLORATION INC.**

Date: APR-03-08


Project:


Attn: **F. SHARPLEY**


We hereby certify the following Assay of 40 CORE samples submitted MAR-26-08 by .


Sample Number	Au g/tonne	Au Check g/tonne	Cu %
50531	Nil	-	0.017
50532	0.01	-	0.019
50533	Nil	-	0.022
50534	Nil	-	0.012
50535	0.07	-	0.019
50536	Nil	-	0.004
50537	0.01	-	0.002
50538	0.01	0.02	0.003
50539	Nil	-	0.004
50540	0.04	-	0.001
BLANK	Nil	-	-
STD OXJ 64	2.43	-	-

Certified by D. Sharpley









2100 m

2200 m

2300 m


2400 m

2500 m


2600 m

E


W







0 200 m



Grid
North

**Opawica Explorations Inc.
ATIKWA LAKE PROPERTY
CLAIM MAP**
Atikwa Lake Twp., Kenora Area, Ontario

UTM Zone 15 Nad 83

October-28-08

1:30000

1000 m

0