

GEOLOGICAL REPORT

CANADIAN ARROW MINES LTD.

“*Prig Property*”
Dryden, Ontario
N.T.S. 052F/10SE

Sudbury, Ontario
January 26, 2009

Jean Bernard
Todd Keast

SUMMARY

In 2008, Canadian Arrow Mines Ltd completed exploration programs on claims in the Turtlepond Lake Area in search for nickel copper platinum group element mineralization. The Prig Property is optioned from Edward Barkauskas (25%) and Sherridan Johnson (75%) Canadian Arrow Mines Ltd has an option agreement with the claim holders to earn a 100% interest in this property. The Prig showings are located 41 km south of the City of Dryden and easily accessible by 502 Highway.

In 2008, an exploration program consisting of airborne VTEM-MAG, geological mapping, prospecting, and ground geophysics, were completed by Canadian Arrow Mines Ltd., on the Prig Property. The work was designed as a preliminary evaluation of the property prior to a diamond drill program.

TABLE OF CONTENTS

1) SUMMARY	i
2) INTRODUCTION	1
3) LOCATION, ACCESS AND OWNERSHIP	2
4) GEOLOGY	6
5) PREVIOUS WORK	7
6) ECONOMIC GEOLOGY	8
7) INTERPRETATION	12
8) CONCLUSION AND RECOMMENDATIONS	15
9) REFERENCES	16

FIGURES

Figure 1: Location map	3
Figure 2: Regional Geology	4
Figure 3: TurtlePond Lake Grids	5
Figure 4: Prig Pit Locations	11
Figure 5: Magnetometer Survey	13
Figure 6: Geophysical + Geological Interpretation	14

TABLES

Table 1: List of the Claim Units	2
Table 2: Summary field work	8
Table 3: Nickel values >0,1%	9
Table 4: Copper values >0,2%	9
Table 5: East Showing	9
Table 6: Pits north of East Showing	10
Table 7: West Showing	10

ANNEXS

Annex 1: Grab Samples Assay Results
Annex 2: Lab Certificates

INTRODUCTION

During the summer months of 2008, Canadian Arrow Mines Ltd. completed an integrated exploration program on a group of claims situated on the northeast lobe of the felsic to intermediate Atikwa-Lawrence Plutonic-Volcanic Complex on the region of north-western Ontario. This report was prepared primarily for the purpose of fulfilling assessment requirements on the property.

Background work involved in the preparation of this report included a review and compilation past exploration work activities by previous operators and a review of work completed by Canadian Arrow Mines Ltd on the Prig Property during the 2008 exploration programs.

In the summer of 2008, Canadian Arrow Mines personnel Tamara Taras (Student Geologist), Fred Paulus (Student Geologist), Jason Patteson (Student Geologist), Peter McChesney (Senior Geologist), Jean Bernard (Senior Geologist) and Todd Keast (P.Geo. Manager) completed geological work on the Prig Showing. The exploration program was directed at evaluating the mafic-ultramafic rocks favourable for hosting nickel-copper-PGM sulphide mineralization.

LOCATION, ACCESS AND OWNERSHIP

The Prig Property is located approximately 41 kilometres drive south of the Town of Dryden, north-western Ontario. The center of the property is at latitude 49°32'50"N, longitude 92°41'W and UTM Nad 83 (Zone 15) coordinates 523500E, 548800N. The property is situated on Claim Map TurtlePond Lake (G-2595), NTS: 052F/10SE.

The property can be reached by driving on Highway 502 for a distance of 40 km south of Dryden. A gravel logging road (Domtar) Snow Flake road is used to travel east 3km. From this point a new trail going south traverses the north center of the claim K4219027 to the south and stops at north-west corner of the claim K-1247472 over a distance of 2.5km.

The Prig Property consists of 1 claim covering four units, situated within Turtlepond Lake Township (Map G2595) of the Kenora Mining Division (**Figure 1**). Edward Barkauskas (25%) and Sheridan Johnson (75%) are the registered holders of claim K-1247472. Canadian Arrow Mines has an option agreement with the claim holders to earn a 100% interest in this property.

The claim K-1247472 (**Figure 2**) is surrounded by 2 unpatented claims consisting one of 11 claim Units and the second of claim 15 Units, which together encompass an area of 500 hectares (table 1). Canadian Arrow Mines Ltd has a 100% interest in these 3 claims. A detailed description of the property which claim number, claim size, claim recording, claim expired date, work in reserve, and work required is included in **Table 1**.

The Prig claims are characterized by moderately abundant bedrock exposures over parts of the area and extensive glacial deposits elsewhere. The topography within the claim group is dominated by two rugged, 30 to 70m high hills, one to the south east of K-4219027, the other to the north of K-1247472. These areas of high ground are separated by low swampy ground. A large spruce sphagnum bog occupies the northeastern corner of the claim K4219030, and




Figure 1 – Project Location

the northern-most K1247472 claim and the eastern part of claim K-4219027 consist largely of a small lakes and large sphagnum bogs.

Table 1 - List of Claims

Claim Number	Recorded	Due Date	Work Required	Total Reserves	Claim Units	Surface (Hectares)
K-1247472	2006-05-29	2009-05-29	\$1 600	\$435	4	64
K-4219027	2007-12-19	2009-12-19	\$6 000	\$5 381	15	240
K-4219030	2007-12-19	2009-12-19	\$4 400	\$3 346	11	196




Figure 2 - Prig Claims and Grid Location

GEOLOGY

The Prig Property is underlain by Archean Aged rocks of the Superior Province of the Canada Shield. It is situated along the western margin of the Dinorwic Lake - Upper Manitou Lake

greenstone belt (**Figure 3**). Satterly (Vol. L, Part 2, OEM Annual Report, 1941, Map No. 50e, The Dryden-Wabigoon Area) indicates that the present property is underlain by diorites,




Figure 3 – Regional Geology

and quartz-hornblende diorites, that comprise the extreme eastern border zones of the very large Atikwa Batholith

The Prig Property is underlain by north-south striking, intermediate to mafic volcanics, locally intercalated with felsic agglomerates and tuffs. These volcanic rocks are intruded by numerous sills of mafic to ultramafic composition. Canadian Arrow Mines Ltd geologists identify the following rock types as underlying the property:

1) Mafic Volcanics:

The volcanic rocks occupy the western part of the Prig grid, with contacts trending north-northeast (**Map 1**). The mafic volcanics are medium to dark green color. The rocks are fine-grained and non-magnetic. The volcanic rocks are locally highly carbonatized and silicified. Several outcrops of altered flows are well exposed along the new road, precisely at the western limit of claims K4219027 and K-4219030 and in the 2008 stripping area. On the eastern side of the Prig grid, two bands of mafic flows reach a few hundred meters in width striking north-northwest to north-northeast.

2) Gabbro:

The gabbro is generally medium to coarse grained, although medium-grained phases with blue quartz eyes are locally developed throughout most of the property. The blue quartz eyes in the gabbroic rock are evidence of an intrusive origin. The unit is medium to dark green in color. The gabbro is the predominant host rock for the nickel copper showings on the Prig grid. On the eastern part of the Prig grid, three major gabbroic sills range between 100 and to 300 meters in thickness, and trend northeast. All three gabbro units are in contact with the mafic volcanics, the topography is controlled by these alternating gabbroic ridges and mafic volcanics lows. Magnetite is locally abundant in the gabbro, and especially in series of outcrops located a few hundred meters east of lines L13+00E and L14+00E and in the big bog area.

3) Pyroxenite:

Pyroxenite underlies two main areas located in the eastern parts of the grid in the vicinity of the two mineralized zones. The pyroxenite appears on the western side of the three gabboic sills with one exception being the western sill where the pyroxenite rocks outcrop on both sides of the gabbro. The base metals showings on Prig grid are hosted within the gabbro pyroxenite.

PREVIOUS WORK

In the 1960's, Alex Glatz (personal communication) was hunting in the area when he discovered a gossanous outcrop, now the eastern most showing of the Prig area. A limited amount of trenching on the showing was completed.

In 1971, Lynx-Canada Explorations Ltd. and Abitibi Asbestos completed electromagnetic and magnetometer surveys over the area. One diamond drill hole was recommended, but never drilled.

In 1977, Beth-Canada Mining Co. did an orientation survey over the known mineralized zones. This survey work consisted of chip sampling of the trenches and a soil sampling program.

In 1987, St.Joe Canada carried out a magnetometer survey and concluded the survey was useful in the geological interpretation of the survey. An Induced Polarization Survey was recommended to detect concentrations of disseminated sulphides prior to diamond drilling.

In September of 1992, Bernard Barton (prospector) sampled and sketched the Korway Glatz Occurrence (Prig Showing). Chips from the pits and the trenches returned 0.8% nickel and 0.4% copper.

2008 EXPLORATION PROGRAM

In the summer of 2008, Canadian Arrow Mines Ltd completed line cutting, prospecting, grab sampling, and ground geophysical surveys over the Prig Property. In August 2008, R.J Meikle & Associates were contracted to perform ground magnetic and inducted polarization surveys over the Prig showings. The results of the geophysical surveys are included in a separate report.

A summary of the field work completed during 2008 is show in **Table 2**. Grid location, geology and old drill holes location, old trenches, pit, and grab samples are show on **Map 1**.

Table 2 - Summary of 2008 Field Work

Grid Name	Gridding (km)	IP Survey (km)	Mag Survey(km)	Grabs	Trenching (m3)
Prig	9,85	4,0	9,85	36	250

A north-south baseline was established using GPS control along the approximate east limit of the claim K-1247472. East-west grid lines were established at 100 meters intervals, with pickets every 25 meters to allow for detailed geological mapping and ground geophysical surveys. A total of 9.85 kilometers of lines were cut on the Prig Property.

In August 2008, a new trail was opened to reach a strong MAG-VTEM anomaly detected on the TurtlePond Lake Property. This road was used to trench trenches the anomaly and for access to the north western portion of the Prig grid.

During the summer of 2008, 36 grab samples were collected in four main areas. Of the 36 grab samples seven samples returned assay values greater than 0.2% combined nickel and copper (**Table 3 and 4**).

Table 3: Nickel >0.1 %

LAB Sample	Ni %	Cu %	Co %	Pt ppm	Pd ppm	Au ppm	S %
397534	0.86	0.61	0.033	0.12	0.351	0.043	11.25
397869	0.615	0.695	0.018	0.048	0.194	0.04	5.25
397868	0.478	0.155	0.035	0.122	0.235	0.041	7.94
397536	0.277	0.363	0.017	0.053	0.123	0.04	2.45
397537	0.128	0.115	0.011	0.02	0.048	0.017	1.06
397867	0.123	0.227	0.019	0.052	0.126	0.017	7.55

Table 4: Copper >0.1%

LAB Sample	Cu %	Ni %	Co %	Pt ppm	Pd ppm	Au ppm	S %
397869	0.695	0.615	0.018	0.048	0.194	0.04	5.25
397534	0.61	0.86	0.033	0.12	0.351	0.043	11.25
397536	0.363	0.277	0.017	0.053	0.123	0.04	2.45
397867	0.227	0.123	0.019	0.052	0.126	0.017	7.55
397535	0.193	0.088	0	0.049	0.088	0.064	0.78
397868	0.155	0.478	0.035	0.122	0.235	0.041	7.94
397537	0.115	0.128	0.011	0.02	0.048	0.017	1.06

1) East Showing:

Six samples (397534, 397601, 397726, 397867, 397868 and 397659) were collected over the five-meter wide, main mineralized zone located on line L15+00N. The East Showing is approximately 30m by 5m wide and trends northwest. Mineralization varies up to 15-20%

combined pyrrhotite and chalcopyrite. The nickel assay values range between 0.12% Ni to 0.86% Ni and between 0.16% Cu and 0.61% Cu. The platinum group elements assay values are range from 0.17 g/t PGM to 0.47 g/t PGM (**Table 5**).

Table 5 - East Showing

LAB Sample	Ni %	Cu %	Co %	Pt ppm	Pd ppm	Au ppm	Ni+Cu %	PGE*
397534	0.86	0.61	0.033	0.12	0.351	0.043	1.47	0,47
397867	0.123	0.227	0.019	0.052	0.126	0.017	0.34	0,17
397868	0.478	0.155	0.035	0.122	0.235	0.041	0.62	0,35

*Platinum Group Elements

2) Pits north of East Showing:

During the 2008 program, a series of pits from work reported by Bernard Barton were re-located 100 m northwest of the East Showing. The samples 397535, 397536 and 397343 were collected in three pits and returned anomalous assay results. (Table 6).

Table 6: Pits north of East Showing

LAB Sample	Ni %	Cu %	Co %	Pt ppm	Pd ppm	Au ppm	Ni+Cu %	PGE*
397536	0.277	0.363	0.017	0.053	0.123	0.04	0.73	0,16
397535	0.088	0.193	0	0.049	0.088	0.064	0.2	0,12
397343	0,023	0,023	0,005	0	0	0	0	0

*Platinum Group Elements

3) West Showing:

Two small pits and one small trench were relocated 150m west of the East Showing. Six samples (397537, 397538, 397869, 397870, 397871 and 397872) were collected in the old works, two samples retuned anomalous assay values (**Table 7**).

Table 7 West Showing

LAB Sample	Ni %	Cu %	Co%	Pt ppm	Pd ppm	Au ppm	Ni+Cu %	PGE*
397869	0.615	0.695	0.018	0.048	0.194	0.04	1.30	0,23
397537	0.128	0.115	0.011	0.02	0.048	0.017	0.23	0,06

*Platinum Group Elements

4) Big Prig Anomaly

In August 2008, six trenches were completed to explain a strong MAG-VTEM anomaly detected on the TurtlePond Lake Property. The outcrops encircling the EM-MAG anomaly are predominately mafic volcanics and contain with 1-5% disseminated pyrrhotite. Eight samples were taken in the six trenches (397563, 397570, 397567, 397568, 397452, 397872,

397656 and 397873), however the samples did not return anomalous base metals or precious metals values.

INTERPRETATION AND RECOMENDATIONS

Results of the geophysical surveys in conjunction with the geological data are presented on **Figure 4**.

According to the geology, the magnetic anomalies located west of base line 40+00E are created by the magnetic sulphides in the mafic volcanics, the stripping area is a good example. Parallel trends of high and low magnetic contours may be seen in both side of the baseline and reflect the magnetic susceptibility of the lithologies.

The East Showing, the historical pits, and IP anomalies are associated with the central gabbroic sill located on lines L14N to L18N, 400m in length, 20m to 50m wide (Figure 6). A second zone hosting the West Showing with associated IP anomalies are extend on lines 12N to 19N, trend north-northwest to north-northeast over an area 800m long by 20m to 50m wide. A VTEM-MAG anomaly is located at the end of lines 14N and 15N, the East Showing and could represent another mineralized zone.

Diamond drilling is recommended to evaluate the main showings. Geological mapping, airborne and ground geophysical surveys have provided sufficient detailed information to plan diamond drill holes.




Figure 4- Geophysical and Geological Interpretation

REFERENCES:

- Balckburn, C.E, Geology of the Boyer lake-Meggisi Lake Area, OGS Report 202, 1981
- Backburn, E.E. Ontario Geological Survey Map 2443, Kenora-Fort-Frances Geological Compilation Series, 1979.
- Backburn, C.E. Hinz, P, Storey C.C, Koloski. L, Ravanas C, 1999, Report of Activities 1998, Resident Geologist Program Ontario Geological Survey Open File report 5987, 88p.
- Barton, B. Geochemical, prospecting, overburden stripping, bedrock trenching (pages 19-20), 1992, 52F16SE0014
- Mc Tavish, A. Flemming, A. St-Joe Canada Inc, magnetometer, 1987, 52F10SE0026, 52F10SE0027.
- Moorhouse, W.W. Geology of eagle Lake Area, OGS, Annual Report Vol KLVIII, 1939.
- Satterly,J. Geology of the Dryden-Wabiggon Area; Ontario Department od Mines, 50th Annual Report, Vol. L, Part II, 1941.

ANNEX -1-


GRAB SAMPLES ASSAY RESULTS

LAB Sample	UTM Nad 83 Zone 15		Rock	Sulphides	Ni	Cu	Co	S
No	Easting	Northing	Type					
396451	522748.0	5488314.0	V3	<1% py	0	0.015	0	0.28
396452	522748.0	5488314.0	V3	<1% po	0	0.018	0	0.35
396453	523115.0	5488704.0	V3	<1% py	0	0	0	0.05
396454	523115.0	5488704.0	V3	tr	0	0	0	0.04
396480	523178.0	5487981.0	QFP	2-3% py	0	0.01	0	0.82
396481	523178.0	5487981.0	QV	nil	0	0	0	0.11
396482	522872.0	5487959.0	V3	4-5% py,po	0.009	0.046	0	3.12
397867	523713.0	5488086.0	I3A	10% Po	0.123	0.227	0.019	7.55
397868	523713.0	5488094.0	I3A/V3	10-15%Po	0.478	0.155	0.035	7.94
397869	523532.0	5488190.0	I3A	15-20%Po-Cpy	0.615	0.695	0.018	5.25
397870	522774.0	5488375.0	I4I/V3	3-5%Po	0	0.013	0	0.29
397871	522774.0	5488375.0	VN Qz		0	0	0	0.07
397872	522776.0	5488370.0	V3		0	0.011	0	0.08
397873	522781.0	5488422.0	I3A		0	0	0	0.08
397725	524108.0	5487916.0	I3A	trace po, cpy	0	0.026	0	0.16
397726	523707.0	5488096.0	I3A	trace po	0.013	0.018	0	0.13
397601	523731.0	5488103.0	I4B	tr-1% py chal	0.038	0.03	0	0.74
397656	522760	5488350	V3		0.011	0.028	0	9.64
397657	523427	5487934	V3		0.012	0.01	0	0.38
397658	523843	5487819	V3		0.011	0.019	0	0.46
397659	523739	5488077	I4B		0.008	0.035	0	13.1
397530	523081.0	5488145.0	I3A	diss po, py	0.01	0.085	0	2.12
397531	523416.0	5488070.0	V3	diss po, py	0.019	0.019	0	0.95
397532	523448.0	5488071.0	I4B	tr po, cpy	0.05	0.007	0	0.11
397533	523544.0	5488075.0	I3A	1% po, cpy	0.013	0.007	0	0.4
397534	523722.0	5488077.0	I4B	15-20% po, cpy	0.86	0.61	0.033	11.25
397535	523645.0	5488149.0	I3A	2-3% po, cpy	0.088	0.193	0	0.78
397536	523647.0	5488160.0	I4B	2-3% po,cpy	0.277	0.363	0.017	2.45
397537	523555.0	5488185.0	I4B	1-2% po, cpy	0.128	0.115	0.011	1.06
397538	523564.0	5488185.0	I4B	1-2% po, cpy	0.082	0.049	0.007	0.75
397539	522890.0	5487988.0	V3	1-2% po, cpy, py	0.01	0.012	0	1.24
397540	523297.0	5488053.0	I3A	tr-1% po, py	0.008	0.008	0	0.48
397343	523700	5488308	I3A	Po3-5%	0.023	0.023	0.005	0.07
397567	522691.0	5488331.0	V3		0.011	0.006	0	0.18
397568	522740.0	5488325.0	V3		0	0.012	0	1.19
397569	522751.0	5488341.0	V3		0.01	0.033	0	13.35
397570	522761.0	5488347.0	V3		0.008	0.028	0	9.32

LAB Sample	UTM Nad 83 Zone 15		Rock	Sulphides	Pt	Pd	Au	S
No	Easting	Northing	Type					
396451	522748.0	5488314.0	V3	<1% py	0	0	0	0.28
396452	522748.0	5488314.0	V3	<1% po	0	0	0	0.35
396453	523115.0	5488704.0	V3	<1% py	0	0	0	0.05
396454	523115.0	5488704.0	V3	tr	0	0	0	0.04
396480	523178.0	5487981.0	QFP	2-3% py	0	0	0	0.82
396481	523178.0	5487981.0	QV	nil	0	0	0.082	0.11
396482	522872.0	5487959.0	V3	4-5% py,po	0	0	0.002	3.12
397867	523713.0	5488086.0	I3A	10% Po	0.052	0.126	0.017	7.55
397868	523713.0	5488094.0	I3A/V3	10-15%Po	0.122	0.235	0.041	7.94
397869	523532.0	5488190.0	I3A	15-20%Po-Cpy	0.048	0.194	0.04	5.25
397870	522774.0	5488375.0	I4I/V3	3-5%Po	0	0	0	0.29
397871	522774.0	5488375.0	VN Qz		0	0	0	0.07
397872	522776.0	5488370.0	V3		0	0	0	0.08
397873	522781.0	5488422.0	I3A		0	0	0	0.08
397725	524108.0	5487916.0	I3A	trace po, cpy	0	0	0	0.16
397726	523707.0	5488096.0	I3A	trace po	0	0	0	0.13
397601	523731.0	5488103.0	I4B	tr-1% py chal	0	0	0	0.74
397656	522760	5488350	V3		0	0	0	9.64
397657	523427	5487934	V3		0	0	0	0.38
397658	523843	5487819	V3		0	0	0	0.46
397659	523739	5488077	I4B		0	0	0	13.1
397530	523081.0	5488145.0	I3A	diss po, py	0	0	0	2.12
397531	523416.0	5488070.0	V3	diss po, py	0	0	0	0.95
397532	523448.0	5488071.0	I4B	tr po, cpy	0	0	0	0.11
397533	523544.0	5488075.0	I3A	1% po, cpy	0	0	0	0.4
397534	523722.0	5488077.0	I4B	15-20% po, cpy	0.12	0.351	0.043	11.25
397535	523645.0	5488149.0	I3A	2-3% po, cpy	0.049	0.088	0.064	0.78
397536	523647.0	5488160.0	I4B	2-3% po,cpy	0.053	0.123	0.04	2.45
397537	523555.0	5488185.0	I4B	1-2% po, cpy	0.02	0.048	0.017	1.06
397538	523564.0	5488185.0	I4B	1-2% po, cpy	0.017	0.032	0	0.75
397539	522890.0	5487988.0	V3	1-2% po, cpy, py	0	0	0	1.24
397540	523297.0	5488053.0	I3A	tr-1% po, py	0	0	0	0.48
397343	523700	5488308	I3A	Po 3-5%	0	0	0	0.07
397567	522691.0	5488331.0	V3		0	0	0	0.18
397568	522740.0	5488325.0	V3		0	0	0	1.19
397569	522751.0	5488341.0	V3		0	0	0.027	13.35
397570	522761.0	5488347.0	V3		0	0	0.01	9.32

ANNEX-2-

LAB CERTIFICATES





ALS Chemex

EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.

212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

To: CANADIAN ARROW MINES LTD.
BRADY SQUARE
233 BRADY STREET, UNIT #8
SUDBURY ON P3B 4H5

Page: 1
Finalized Date: 12-JUL-2008
Account: CNARMN

CERTIFICATE TB08081561

Project:

P.O. No.:

This report is for 58 Rock samples submitted to our lab in Thunder Bay, ON, Canada on 20-JUN-2008.

The following have access to data associated with this certificate:

TODD KEAST

DEAN MACEACHERN

ACCOUNTS PAYABLE

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
CRU-QC	Crushing QC Test
PUL-QC	Pulverizing QC Test
PUL-31	Pulverize split to 85% <75 um

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
ME-ICP81	ICP Fusion - Ore Grade	ICP-AES
Ag-AA62	Ore grade Ag - four acid /AAS	AAS
Au-AA23	Au 30g FA-AA finish	AAS
PGM-ICP23	Pt, Pd, Au 30g FA ICP	ICP-AES

To: CANADIAN ARROW MINES LTD.
ATTN: TODD KEAST
BRADY SQUARE
233 BRADY STREET, UNIT #8
SUDBURY ON P3B 4H5

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature:

Colin Ramshaw, Vancouver Laboratory Manager



ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

To: CANADIAN ARROW MINES LTD.
BRADY SQUARE
233 BRADY STREET, UNIT #8
SUDBURY ON P3B 4H5

Page: 2 - A
Total # Pages: 3 (A)
Finalized Date: 12-JUL-2008
Account: CNARMN

CERTIFICATE OF ANALYSIS TB08081561

Sample Description	Method	WEI-21	ME-ICP81	ME-ICP81	ME-ICP81	PGM-ICP23	PGM-ICP23	PGM-ICP23	Ag-AA62	ME-ICP81	Au-AA23
	Analyte Units	Recv'd Wt.	Ni	Cu	Co	Pt	Pd	Au	Ag	S	Au
	LOR	kg	%	%	%	ppm	ppm	ppm	ppm	%	ppm
396480		1.16	0.008	0.010	0.002	<0.005	0.002	<0.001	1	0.82	
396481		0.97	<0.005	<0.005	<0.002	<0.005	<0.001	0.082	<1	0.11	
396482		0.95	0.009	0.046	0.006	<0.005	0.001	0.002	1	3.12	
396483		0.91								<0.005	
396484		1.20								<0.005	
396485		1.51								<0.005	
396486		1.08								<0.005	
396487		0.95								0.148	
396488		1.55								0.216	
396489		1.43								0.273	
396490		1.15								0.105	
396491		2.26								0.059	
396492		2.24								0.170	
396493		1.04								<0.005	
396494		1.77	0.009	0.008	0.005	<0.005	<0.001	<0.001	<1	0.23	
396495		0.76	0.017	0.097	0.008	<0.005	0.001	0.501	2	2.00	
396496		1.48	<0.005	1.140	0.004	<0.005	0.014	0.289	8	1.34	
396497		1.31	0.016	0.193	0.005	<0.005	0.003	0.036	3	0.52	
396498		0.99	0.105	0.081	0.030	<0.005	0.007	0.021	2	14.75	
396499		1.27	0.033	0.215	0.008	<0.005	0.004	<0.001	1	0.18	
396500		1.20	0.100	0.359	0.011	0.048	0.045	0.017	2	1.33	
397601		1.38	0.038	0.030	0.006	<0.005	0.008	<0.001	<1	0.74	
397602		1.87	0.389	1.045	0.257	0.013	0.094	0.008	1	23.1	
397709		1.32	0.107	0.064	0.010	0.188	0.261	0.008	<1	0.54	
397710		0.58	0.212	0.431	0.009	0.208	0.156	0.090	2	1.05	
397711		2.48	0.025	0.028	0.014	<0.005	0.002	0.016	<1	12.40	
397712		1.74	0.019	0.016	0.004	<0.005	0.002	0.001	<1	1.83	
397713		2.49	0.021	0.011	0.005	<0.005	0.001	0.002	<1	4.23	
397714		1.55	<0.005	0.010	0.003	<0.005	<0.001	<0.001	<1	0.29	
397715		2.06	0.012	0.010	0.003	<0.005	<0.001	<0.001	<1	4.49	
397716		0.71	0.019	0.063	0.005	<0.005	0.001	0.007	<1	0.20	
397717		3.52	0.013	0.013	0.004	<0.005	0.001	0.001	<1	2.25	
397718		1.12	0.225	0.209	0.014	0.010	0.008	0.035	<1	1.68	
397719		1.21	0.018	0.008	0.003	<0.005	<0.001	0.001	<1	5.62	
397720		2.14	0.067	0.053	0.007	<0.005	0.002	0.005	<1	0.31	
397721		2.19	0.202	0.587	0.006	0.204	0.148	0.088	1	3.87	
397722		1.39	<0.005	0.012	<0.002	<0.005	<0.001	0.058	<1	1.28	
397723		1.66	0.115	0.093	0.011	0.067	0.044	0.049	<1	0.93	
397724		1.34	0.006	<0.005	<0.002	<0.005	<0.001	0.001	<1	1.26	
397725		1.84	<0.005	0.026	0.002	<0.005	<0.001	0.007	1	0.16	



ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brookbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

To: CANADIAN ARROW MINES LTD.
BRADY SQUARE
233 BRADY STREET, UNIT #8
SUDBURY ON P3B 4H5

Page: 3 - A
Total # Pages: 3 (A)
Finalized Date: 12-JUL-2008
Account: CNARMN

CERTIFICATE OF ANALYSIS TB08081561

Sample Description	Method	WEI-21	ME-ICP81	ME-ICP81	ME-ICP81	PGM-ICP23	PGM-ICP23	PGM-ICP23	Ag-AA62	ME-ICP81	Au-AA23
	Analyte	Recv'd Wt.	Ni	Cu	Co	Pt	Pd	Au	Ag	S	Au
	Units	kg	%	%	%	ppm	ppm	ppm	ppm	%	ppm
Method	Analyst	Recv'd Wt.	Ni	Cu	Co	Pt	Pd	Au	Ag	S	Au
Sample Description	Units	kg	%	%	%	ppm	ppm	ppm	ppm	%	ppm
Sample Description	LOR	0.02	0.005	0.005	0.002	0.005	0.001	0.001	1	0.01	0.005
397726		1.46	0.013	0.018	0.002	<0.005	0.002	0.004	<1	0.13	
397727		1.33	0.025	0.031	0.013	<0.005	0.004	0.003	2	14.55	
397728		1.15	<0.005	<0.005	<0.002	<0.005	<0.001	<0.001	<1	0.06	
397729		1.36	<0.005	<0.005	<0.002	<0.005	<0.001	<0.001	1	0.03	
397730		0.96	0.019	0.026	0.007	0.005	0.001	0.004	1	1.33	
397731		2.01	0.015	0.105	0.011	<0.005	0.002	0.001	1	4.03	
397801		1.86	0.158	0.360	0.014	0.032	0.034	0.014	2	1.55	
397802		1.08	0.043	0.515	0.006	0.098	0.101	0.033	6	0.74	
397803		1.74	0.077	1.025	0.006	0.260	0.383	0.049	8	1.24	
397804		0.71	0.056	0.208	0.014	0.013	0.021	0.009	1	2.61	
397805		1.61	0.029	0.155	0.006	0.028	0.034	0.007	1	0.96	
397806		2.22	0.171	0.402	0.014	0.066	0.047	0.028	2	2.27	
397807		2.59	0.173	0.234	0.020	<0.005	0.006	0.009	1	2.32	
397808		1.99	2.23	0.086	0.188	0.018	0.086	0.012	1	28.4	
397809		1.23	2.49	0.401	0.315	0.012	0.050	0.040	2	36.9	
397810		0.57	2.37	0.435	0.202	<0.005	0.075	0.011	1	29.2	
397811		0.81	0.133	0.593	0.015	0.037	0.048	0.072	2	1.99	
397812		1.36	0.190	0.215	0.022	0.005	0.007	0.007	1	2.33	



ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.

212 Brookbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

To: CANADIAN ARROW MINES LTD.
236 CEDAR ST
SUDBURY ON P3B 1M7

Page: 1

Finalized Date: 19-JUN-2008

Account: CNARMN

CERTIFICATE TB08072722

Project:

P.O. No.:

This report is for 85 Rock samples submitted to our lab in Thunder Bay, ON, Canada on 4-JUN-2008.

The following have access to data associated with this certificate:

TODD KEAST

DEAN MACEACHERN

ACCOUNTS PAYABLE

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
CRU-QC	Crushing QC Test
PUL-QC	Pulverizing QC Test
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
ME-ICP81	ICP Fusion - Ore Grade	ICP-AES
Ag-AA62	Ore grade Ag - four acid /AAS	AAS
PGM-ICP23	Pt, Pd, Au 30g FA ICP	ICP-AES

To: CANADIAN ARROW MINES LTD.
ATTN: TODD KEAST
236 CEDAR ST
SUDBURY ON P3B 1M7

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature:


Colin Ramshaw, Vancouver Laboratory Manager



ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.

212 Brookbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

To: CANADIAN ARROW MINES LTD.
236 CEDAR ST
SUDBURY ON P3B 1M7

Page: 2 - A
Total # Pages: 4 (A)
Finalized Date: 19-JUN-2008
Account: CNARMN

CERTIFICATE OF ANALYSIS TB08072722

Sample Description	Method	WEI-21	ME-ICP81	ME-ICP81	ME-ICP81	PGM-ICP23	PGM-ICP23	PGM-ICP23	Ag-AA62	ME-ICP81
	Analyte	Recv'd Wt.	Ni	Cu	Co	Pt	Pd	Au	Ag	S
	Units	kg	%	%	%	ppm	ppm	ppm	ppm	%
Method	Analyst	Recvd Wt.	Ni	Cu	Co	Pt	Pd	Au	Ag	S
Sample Description	Units	kg	%	%	%	ppm	ppm	ppm	ppm	%
Sample Description	LOR	0.02	0.005	0.005	0.002	0.005	0.001	0.001	1	0.01
DRH-01		0.99	0.005	0.017	0.005	<0.005	0.002	0.005	<1	10.90
DRH-02		0.98	<0.005	<0.005	0.002	<0.005	0.001	0.003	<1	11.00
DRH-03		1.23	<0.005	0.069	0.012	<0.005	0.003	0.010	<1	2.97
DRH-04		1.51	0.019	0.102	0.009	<0.005	0.001	0.004	1	7.00
DRH-05		1.71	0.046	0.103	0.011	0.024	0.070	0.005	<1	0.68
DRH-06		1.04	0.008	0.019	0.003	0.009	0.006	0.005	<1	0.51
DRH-07		0.76	<0.005	0.033	0.009	0.008	0.001	0.002	<1	2.72
DRH-08		1.69	0.008	0.011	0.002	<0.005	0.001	0.003	<1	1.96
DRH-09		1.53	<0.005	<0.005	0.004	<0.005	<0.001	0.002	<1	0.23
DRH-10		1.21	0.022	0.006	0.004	<0.005	<0.001	0.002	<1	0.10
DRH-11		1.05	<0.005	<0.005	0.005	<0.005	<0.001	0.002	<1	0.21
DRH-12		1.41	<0.005	0.005	<0.002	<0.005	<0.001	0.002	1	1.22
DRH-13		0.71	0.010	<0.005	0.004	<0.005	0.001	0.002	<1	1.72
DRH-14		2.00	0.015	0.021	0.008	<0.005	0.001	0.007	1	17.35
DRH-15		0.84	0.006	0.038	0.002	<0.005	<0.001	0.003	<1	0.64
DRH-16		0.92	0.022	0.022	0.005	0.010	0.015	0.002	<1	1.57
DRH-17		1.78	0.009	0.032	0.006	<0.005	0.002	0.003	1	6.69
DRH-18		1.86	0.416	0.041	0.042	<0.005	0.035	0.005	<1	17.40
DRH-19		1.25	0.060	0.031	0.012	0.006	0.014	0.002	<1	0.40
DRH-20		1.63	<0.005	<0.005	<0.002	<0.005	0.001	0.001	<1	0.05
DRH-21		2.80	0.013	0.041	0.010	<0.005	<0.001	0.002	<1	5.92
DRH-22		1.29	0.492	0.544	0.139	0.023	0.038	0.005	1	21.8
DRH-23		1.28	0.382	2.34	0.057	<0.005	0.211	0.012	5	20.0
DRH-24		1.69	0.210	1.170	0.027	<0.005	0.037	0.011	3	10.15
396451		1.04	0.005	0.015	0.002	<0.005	0.001	0.002	<1	0.28
396452		1.21	<0.005	0.018	<0.002	<0.005	0.001	0.008	1	0.35
396453		1.05	0.006	<0.005	<0.002	<0.005	0.001	0.003	<1	0.05
396454		0.92	<0.005	<0.005	<0.002	<0.005	<0.001	0.001	<1	0.04
396455		1.00	0.006	0.005	0.002	<0.005	0.001	0.002	<1	0.54
396456		1.69	0.053	0.082	0.007	<0.005	0.005	0.015	1	0.71
396457		1.12	0.010	0.013	0.003	<0.005	0.002	0.002	1	0.35
396458		2.09	0.224	0.410	0.027	0.010	0.050	0.022	2	4.59
396459		2.29	0.099	0.227	0.014	0.005	0.015	0.041	2	2.06
396460		1.48	0.012	0.009	0.003	<0.005	0.002	0.005	1	0.04
396461		1.72	0.085	0.046	0.007	0.028	0.036	0.003	<1	1.49
396462		1.61	0.017	0.075	0.004	<0.005	0.001	0.003	1	0.47
396463		2.06	0.014	0.487	0.005	0.012	0.032	0.033	6	0.63
396464		1.67	0.011	0.104	0.005	<0.005	0.002	0.008	2	0.30
396465		1.53	0.086	0.202	0.018	0.007	0.007	0.022	2	2.44
396466		4.37	0.006	0.039	0.004	<0.005	0.001	0.004	<1	0.53



ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.

212 Brookbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

To: CANADIAN ARROW MINES LTD.
236 CEDAR ST
SUDBURY ON P3B 1M7

Page: 3 - A
Total # Pages: 4 (A)
Finalized Date: 19-JUN-2008
Account: CNARMN

CERTIFICATE OF ANALYSIS TB08072722

Sample Description	Method	WEI-21	ME-ICP81	ME-ICP81	ME-ICP81	PGM-ICP23	PGM-ICP23	PGM-ICP23	Ag-AA62	ME-ICP81
	Analyte	Recv Wt.	Ni	Cu	Co	Pt	Pd	Au	Ag	S
	Units	kg	%	%	%	ppm	ppm	ppm	ppm	%
Method	Analyst	Recvd Wt.	Ni	Cu	Co	Pt	Pd	Au	Ag	S
Sample Description	Units	kg	%	%	%	ppm	ppm	ppm	ppm	%
Sample Description	LOR	0.02	0.005	0.005	0.002	0.005	0.001	0.001	1	0.01
396467		1.10	<0.005	0.019	<0.002	<0.005	<0.001	0.011	<1	0.61
396468		2.50	0.011	0.048	0.006	<0.005	<0.001	0.001	<1	2.56
396469		1.12	<0.005	0.016	0.002	<0.005	<0.001	0.002	<1	0.91
396470		1.69	0.049	0.046	0.005	<0.005	<0.001	0.005	<1	0.16
396471		1.16	<0.005	0.051	<0.002	<0.005	<0.001	0.003	1	1.09
396472		1.22	0.028	0.047	0.003	<0.005	<0.001	0.006	1	0.14
396473		1.27	0.076	0.199	0.009	<0.005	0.002	0.036	2	1.33
396474		1.19	0.169	0.153	0.011	<0.005	0.002	0.019	<1	1.78
396475		1.07	0.088	0.177	0.008	<0.005	0.005	0.023	1	1.12
396476		1.27	0.005	0.010	0.002	<0.005	<0.001	0.008	1	2.27
396477		1.54	0.159	0.126	0.013	<0.005	0.003	0.003	1	1.85
396478		1.66	0.011	0.015	0.004	<0.005	0.003	0.003	<1	2.08
396479		1.05	0.008	0.005	0.002	<0.005	<0.001	<0.001	<1	0.28
397701		1.69	0.072	0.058	0.006	<0.005	0.002	0.002	1	0.51
397702		1.26	0.056	0.057	0.005	<0.005	0.001	0.009	<1	0.40
397703		2.55	0.037	0.134	0.008	0.027	0.022	<0.001	<1	1.12
397704		0.50	<0.005	<0.005	<0.002	<0.005	<0.001	<0.001	<1	0.01
397705		2.22	0.076	0.138	0.012	0.030	0.036	0.001	<1	2.37
397706		0.74	<0.005	<0.005	<0.002	<0.005	<0.001	<0.001	<1	0.07
397707		0.84	<0.005	<0.005	<0.002	<0.005	<0.001	<0.001	<1	0.01
397708		1.47	<0.005	0.007	0.003	<0.005	0.002	<0.001	<1	0.18
397851		0.36	0.136	0.065	0.008	0.023	0.019	0.012	<1	0.59
397852		0.59	0.006	<0.005	<0.002	<0.005	<0.001	0.001	<1	1.07
397853		0.48	0.087	0.058	0.009	0.023	0.020	0.028	<1	0.64
397854		0.30	0.060	0.008	0.005	0.006	0.005	0.003	<1	0.08
397855		0.59	0.147	1.550	0.007	0.203	0.165	0.098	4	2.66
397856		0.48	0.067	0.036	0.006	0.010	0.007	0.006	<1	0.13
397857		1.41	0.107	0.094	0.008	0.094	0.087	0.114	1	1.06
397858		0.73	0.005	0.007	0.003	<0.005	0.001	0.009	<1	1.05
397859		0.56	0.008	0.008	0.003	<0.005	<0.001	0.994	5	3.43
397860		0.39	<0.005	0.015	0.002	<0.005	0.001	0.035	<1	0.66
397861		0.51	0.009	0.023	0.003	<0.005	0.001	0.005	<1	1.22
397862		0.66	0.011	0.040	0.004	<0.005	0.001	0.002	<1	2.12
397863		0.44	0.007	0.006	0.003	<0.005	<0.001	0.431	1	5.96
397864		0.50	<0.005	<0.005	<0.002	<0.005	<0.001	0.036	<1	0.23
397865		0.45	0.016	0.006	0.003	<0.005	0.001	0.604	5	2.78
397866		0.47	<0.005	0.007	<0.002	<0.005	<0.001	0.003	<1	0.45
397867		0.52	0.123	0.227	0.019	0.052	0.126	0.017	1	7.55
397868		0.64	0.478	0.155	0.035	0.122	0.235	0.041	<1	7.94
397869		0.78	0.615	0.695	0.018	0.048	0.194	0.040	3	5.25



ALS Chemex

EXCELLENCE IN ANALYTICAL CHEMISTRY

ALS Canada Ltd.

212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

To: CANADIAN ARROW MINES LTD.
236 CEDAR ST
SUDBURY ON P3B 1M7

Page: 4 - A
Total # Pages: 4 (A)
Finalized Date: 19-JUN-2008
Account: CNARMN

CERTIFICATE OF ANALYSIS TB08072722



ALS Chemex

EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.

212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

To: CANADIAN ARROW MINES LTD.
BRADY SQUARE
233 BRADY STREET, UNIT #8
SUDBURY ON P3B 4H5

Page: 1

Finalized Date: 24-OCT-2008

Account: CNARMN

CERTIFICATE TB08138915

Project:

P.O. No.:

This report is for 32 Rock samples submitted to our lab in Thunder Bay, ON, Canada on 30-SEP-2008.

The following have access to data associated with this certificate:

TODD KEAST

DEAN MACEACHERN

ACCOUNTS PAYABLE

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
CRU-QC	Crushing QC Test
PUL-QC	Pulverizing QC Test
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
ME-ICP81	ICP Fusion - Ore Grade	ICP-AES
Ag-AA62	Ore grade Ag - four acid /AAS	AAS
PGM-ICP23	Pt, Pd, Au 30g FA ICP	ICP-AES

To: CANADIAN ARROW MINES LTD.
ATTN: TODD KEAST
BRADY SQUARE
233 BRADY STREET, UNIT #8
SUDBURY ON P3B 4H5

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature:



Colin Ramshaw, Vancouver Laboratory Manager



ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brookbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

To: CANADIAN ARROW MINES LTD.
BRADY SQUARE
233 BRADY STREET, UNIT #8
SUDBURY ON P3B 4H5

Page: 2 - A
Total # Pages: 2 (A)
Finalized Date: 24-OCT-2008
Account: CNARMN

CERTIFICATE OF ANALYSIS TB08138915

Sample Description	Method	WEI-21	ME-ICP81	ME-ICP81	ME-ICP81	PGM-ICP23	PGM-ICP23	PGM-ICP23	Ag-AA62	ME-ICP81
	Analyte	Recv Wt.	Ni	Cu	Co	Pt	Pd	Au	Ag	S
	Units	kg	%	%	%	ppm	ppm	ppm	ppm	%
Method	Analyst	Recvd Wt.	Ni	Cu	Co	Pt	Pd	Au	Ag	S
Sample Description	Units	kg	%	%	%	ppm	ppm	ppm	ppm	%
Sample Description	LOR	0.02	0.005	0.005	0.002	0.005	0.001	0.001	1	0.01
397331		1.57	0.006	0.011	0.002	0.006	0.005	0.005	<1	0.95
397332		2.00	<0.005	0.028	0.002	<0.005	<0.001	0.002	1	0.38
397333		3.66	0.008	0.933	0.016	<0.005	0.001	0.120	3	4.66
397334		4.43	0.006	0.429	0.010	<0.005	<0.001	0.374	2	2.73
397335		4.15	0.009	0.400	0.005	<0.005	<0.001	0.022	1	1.20
397336		1.13	0.005	0.014	<0.002	0.005	0.003	0.002	<1	0.06
397337		1.87	0.834	0.062	0.027	<0.005	<0.001	0.002	1	0.40
397338		1.26	0.005	0.115	0.004	<0.005	<0.001	0.043	1	0.53
397339		2.90	<0.005	0.158	0.004	<0.005	<0.001	0.008	1	1.60
397340		4.33	0.016	0.588	0.009	<0.005	<0.001	0.007	1	2.87
397341		1.49	0.006	0.023	0.017	<0.005	0.002	0.022	1	7.78
397342		1.58	0.013	3.10	0.016	<0.005	0.002	0.834	11	4.53
397343		1.05	0.023	0.023	0.005	<0.005	0.001	0.005	1	0.07
397617		1.71	0.178	0.247	0.008	0.013	0.023	0.020	2	1.83
397618		1.52	0.487	0.399	0.024	0.067	0.120	0.047	4	5.52
397619		2.77	0.040	0.022	0.005	<0.005	0.003	<0.001	1	0.57
397620		2.07	0.028	0.034	0.005	<0.005	<0.001	0.001	1	0.68
H179641		1.14	0.013	0.019	0.003	0.005	<0.001	<0.001	1	0.28
H179642		0.80	0.017	0.031	0.005	<0.005	<0.001	<0.001	1	0.84
H179643		0.92	0.013	0.012	0.004	<0.005	<0.001	<0.001	1	0.92
H179644		1.17	0.010	0.006	0.003	<0.005	<0.001	<0.001	1	0.18
H179645		1.25	0.005	0.008	0.003	0.007	0.007	<0.001	1	1.09
H179701		2.60	0.006	0.006	<0.002	<0.005	<0.001	0.001	<1	2.02
H179702		4.09	0.345	0.263	0.016	0.006	0.007	0.032	2	4.12
H179703		3.61	0.019	0.026	0.005	0.005	0.002	0.003	1	0.44
H179704		2.66	0.038	0.033	0.004	<0.005	0.003	0.006	1	0.50
H179705		1.82	0.021	0.025	0.006	<0.005	<0.001	0.006	1	0.04
H179706		2.05	0.083	0.111	0.012	0.007	0.002	0.015	1	0.89
H179707		1.76	0.237	0.285	0.018	<0.005	0.005	0.037	3	2.73
H179708		2.80	0.022	0.020	0.003	<0.005	<0.001	0.001	1	0.15
H179709		2.90	0.188	0.031	0.005	<0.005	<0.001	0.010	2	0.02
H179710		2.37	0.032	0.011	0.005	<0.005	<0.001	0.003	2	0.04



ALS Chemex

EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.

212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

To: CANADIAN ARROW MINES LTD.
BRADY SQUARE
233 BRADY STREET, UNIT #8
SUDBURY ON P3B 4H5

Page: 1
Finalized Date: 18-SEP-2008
Account: CNARMN

CERTIFICATE TB08124380

Project: GLATZ

P.O. No.:

This report is for 38 Rock samples submitted to our lab in Thunder Bay, ON, Canada on 3-SEP-2008.

The following have access to data associated with this certificate:

TODD KEAST

DEAN MACEACHERN

ACCOUNTS PAYABLE

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
CRU-QC	Crushing QC Test
PUL-QC	Pulverizing QC Test
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
ME-ICP81	ICP Fusion - Ore Grade	ICP-AES
Ag-AA62	Ore grade Ag - four acid /AAS	AAS
PGM-ICP23	Pt, Pd, Au 30g FA ICP	ICP-AES

To: CANADIAN ARROW MINES LTD.
ATTN: TODD KEAST
BRADY SQUARE
233 BRADY STREET, UNIT #8
SUDBURY ON P3B 4H5

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature:

Colin Ramshaw, Vancouver Laboratory Manager



ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brookbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

To: CANADIAN ARROW MINES LTD.
BRADY SQUARE
233 BRADY STREET, UNIT #8
SUDBURY ON P3B 4H5

Page: 2 - A
Total # Pages: 2 (A)
Finalized Date: 18-SEP-2008
Account: CNARMN

Project: GLATZ

CERTIFICATE OF ANALYSIS TB08124380

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt.	ME-ICP81 Ni %	ME-ICP81 Cu %	ME-ICP81 Co %	PGM-ICP23 Pt ppm	PGM-ICP23 Pd ppm	PGM-ICP23 Au ppm	Ag-AA62 Ag ppm	ME-ICP81 S %
		kg	0.02	0.005	0.005	0.002	0.005	0.001	0.001	0.01
397107		2.32	0.289	1.725	0.077	0.008	0.019	0.191	11	13.05
397544		2.70	0.417	0.215	0.026	<0.005	0.004	0.003	2	4.76
397545		1.21	0.134	0.183	0.008	<0.005	0.004	0.004	1	0.89
397546		2.04	0.041	0.065	0.007	<0.005	0.003	0.001	1	1.95
397547		1.53	0.179	0.384	0.010	0.007	0.009	0.014	2	1.69
397548		1.53	0.058	0.053	0.007	<0.005	0.001	0.001	1	0.53
397549		2.84	0.052	0.155	0.006	<0.005	0.002	0.019	2	0.41
397550		2.68	0.165	0.465	0.014	<0.005	0.003	0.083	3	3.27
397551		3.14	0.111	0.144	0.007	<0.005	0.003	0.024	1	0.91
397552		2.03	0.130	0.550	0.018	<0.005	0.005	0.080	3	3.29
397553		2.38	0.209	0.219	0.012	<0.005	0.004	0.027	2	1.70
397554		3.02	0.344	0.648	0.027	0.006	0.008	0.008	4	5.62
397555		2.68	0.096	0.100	0.007	<0.005	0.001	0.010	1	0.89
397556		2.47	0.115	2.35	0.062	0.006	0.004	0.199	16	10.25
397557		2.27	0.226	0.342	0.020	<0.005	0.005	0.050	2	3.48
397558		2.55	0.409	0.226	0.020	<0.005	0.003	0.027	<1	4.10
397559		2.06	0.261	0.548	0.018	<0.005	0.007	0.063	3	4.98
397560		1.66	0.349	0.176	0.017	<0.005	0.005	0.026	2	2.82
397561		1.88	0.100	0.123	0.011	<0.005	0.001	0.029	1	1.34
397562		2.77	0.148	0.203	0.009	<0.005	0.002	0.015	2	1.99
397563		1.29	0.132	0.349	0.008	<0.005	0.005	0.032	4	1.49
397564		1.64	0.234	0.316	0.010	<0.005	0.002	0.011	2	2.13
397565		1.53	0.059	0.047	0.007	<0.005	0.003	0.002	1	0.22
397566		3.82	0.190	0.145	0.017	<0.005	0.006	0.003	1	2.51
397567		1.77	0.011	0.006	0.003	<0.005	<0.001	<0.001	1	0.18
397568		2.21	<0.005	0.012	0.003	<0.005	<0.001	0.001	<1	1.19
397569		2.53	0.010	0.033	0.006	<0.005	0.002	0.027	<1	13.35
397570		1.26	0.008	0.028	0.004	<0.005	0.001	0.010	2	9.32
397661		2.52	<0.005	<0.005	0.004	<0.005	<0.001	<0.001	<1	0.13
397662		3.03	0.323	0.282	0.025	0.005	0.005	0.011	2	4.08
397663		2.27	0.075	0.043	0.008	0.005	0.005	0.004	1	0.24
397664		2.79	0.104	0.094	0.008	0.007	0.006	0.012	1	0.69
397665		2.56	0.110	0.113	0.007	<0.005	0.002	0.007	2	0.46
397666		2.76	0.165	0.155	0.010	<0.005	0.004	0.004	2	1.58
397667		3.08	0.177	0.146	0.011	<0.005	0.003	0.002	1	1.67
397668		2.29	0.056	0.021	0.010	<0.005	0.001	0.014	1	0.05
397669		2.67	0.070	0.061	0.008	<0.005	0.002	0.002	<1	0.78
397670		2.63	0.127	0.113	0.010	<0.005	0.003	0.003	1	1.57



ALS Chemex

EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.

212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

To: CANADIAN ARROW MINES LTD.
BRADY SQUARE
233 BRADY STREET, UNIT #8
SUDBURY ON P3B 4H5

Page: 1

Finalized Date: 28-AUG-2008

Account: CNARMN

CERTIFICATE TB08109312

Project:

P.O. No.:

This report is for 98 Rock samples submitted to our lab in Thunder Bay, ON, Canada on 7-AUG-2008.

The following have access to data associated with this certificate:

TODD KEAST

DEAN MACEACHERN

ACCOUNTS PAYABLE

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
CRU-QC	Crushing QC Test
PUL-QC	Pulverizing QC Test
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
ME-ICP81	ICP Fusion - Ore Grade	ICP-AES
Ag-AA62	Ore grade Ag - four acid /AAS	AAS
PGM-ICP23	Pt, Pd, Au 30g FA ICP	ICP-AES

To: CANADIAN ARROW MINES LTD.
ATTN: TODD KEAST
BRADY SQUARE
233 BRADY STREET, UNIT #8
SUDBURY ON P3B 4H5

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature:

Colin Ramshaw, Vancouver Laboratory Manager



ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brookbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

To: CANADIAN ARROW MINES LTD.
BRADY SQUARE
233 BRADY STREET, UNIT #8
SUDBURY ON P3B 4H5

Page: 2 - A
Total # Pages: 4 (A)
Finalized Date: 28-AUG-2008
Account: CNARMN

CERTIFICATE OF ANALYSIS TB08109312

Sample Description	Method	WEI-21	ME-ICP81	ME-ICP81	ME-ICP81	PGM-ICP23	PGM-ICP23	PGM-ICP23	Ag-AA62	ME-ICP81
	Analyte	Recv Wt.	Ni	Cu	Co	Pt	Pd	Au	Ag	S
	Units	kg	%	%	%	ppm	ppm	ppm	ppm	%
Method	Analyst	Recvd Wt.	Ni	Cu	Co	Pt	Pd	Au	Ag	S
Sample Description	Units	kg	%	%	%	ppm	ppm	ppm	ppm	%
Sample Description	LOR	0.02	0.005	0.005	0.002	0.005	0.001	0.001	1	0.01
397101		2.95	<0.005	0.044	0.035	<0.005	<0.001	0.163	1	12.75
397102		2.45	<0.005	0.016	0.005	<0.005	<0.001	0.005	<1	0.48
397103		3.20	<0.005	0.023	0.005	<0.005	0.002	0.005	<1	1.66
397104		2.13	<0.005	0.012	0.005	<0.005	<0.001	0.001	<1	1.94
397105		2.25	<0.005	0.015	0.004	0.005	0.001	0.003	<1	0.79
397106		2.18	<0.005	0.010	0.004	<0.005	<0.001	0.001	<1	0.69
397264		0.52	<0.005	<0.005	0.009	0.007	<0.001	0.006	<1	7.15
397265		0.65	<0.005	0.018	0.003	0.007	0.001	0.121	<1	1.61
397266		1.83	<0.005	0.016	0.005	0.005	<0.001	0.002	<1	6.10
397267		1.47	<0.005	0.013	0.002	<0.005	<0.001	0.002	<1	3.54
397268		0.74	<0.005	0.020	0.004	0.011	0.007	0.042	<1	1.71
397269		0.56	<0.005	0.017	0.004	0.006	0.003	0.009	<1	2.16
397270		0.90	<0.005	0.017	0.002	<0.005	<0.001	0.004	<1	2.32
397271		1.29	<0.005	0.005	<0.002	<0.005	<0.001	0.002	<1	1.25
397272		0.56	<0.005	0.009	0.006	<0.005	<0.001	0.004	<1	0.30
397273		0.47	<0.005	0.020	0.005	0.015	0.004	0.005	<1	0.38
397274		1.00	0.008	<0.005	0.002	0.007	0.001	0.003	<1	0.61
397275		0.31	<0.005	0.006	0.002	0.007	0.002	0.003	<1	0.57
397276		0.78	<0.005	0.009	0.002	0.007	0.001	0.006	<1	1.61
397277		1.04	<0.005	0.008	0.002	<0.005	0.001	0.003	<1	2.31
397278		0.69	<0.005	0.011	0.005	<0.005	<0.001	0.002	<1	0.24
397279		0.62	0.006	<0.005	0.003	0.005	<0.001	0.001	<1	0.15
397280		0.43	0.016	0.026	0.005	0.007	0.001	0.001	<1	0.16
397281		0.56	0.008	0.019	0.006	<0.005	0.003	0.002	<1	2.13
397282		1.05	0.211	0.196	0.015	0.028	0.026	0.019	1	1.43
397283		1.54	0.100	0.106	0.010	0.027	0.022	0.016	1	0.76
397284		0.97	0.088	0.116	0.009	0.023	0.019	0.037	1	0.57
397285		0.37	0.046	0.033	0.012	0.005	0.003	0.005	<1	0.89
397286		1.22	0.102	0.061	0.006	0.236	0.340	0.078	1	0.30
397287		1.22	0.113	0.113	0.008	0.098	0.200	0.084	1	0.60
397288		0.91	0.128	0.215	0.008	0.178	0.324	0.126	1	0.90
397289		1.24	0.005	0.009	0.002	<0.005	0.003	0.003	<1	1.45
397290		0.59	0.019	0.022	0.005	<0.005	0.008	0.019	<1	18.25
397291		1.80	0.016	0.015	0.003	0.005	0.002	0.002	<1	2.16
397292		0.69	0.007	0.028	<0.002	<0.005	<0.001	0.019	<1	0.97
397293		0.93	0.005	0.025	0.003	<0.005	<0.001	0.002	<1	0.80
397294		0.69	0.006	0.021	0.003	0.015	0.014	0.009	<1	0.61
397295		1.01	0.118	0.203	0.013	0.015	0.032	0.002	1	2.01
397296		1.21	0.072	0.046	0.007	0.009	0.007	0.005	<1	0.12
397297		0.44	0.014	0.007	<0.002	<0.005	0.003	0.005	<1	0.24



CERTIFICATE OF ANALYSIS TB08109312

Sample Description	Method	WEI-21	ME-ICP81	ME-ICP81	ME-ICP81	PGM-ICP23	PGM-ICP23	PGM-ICP23	Ag-AA62	ME-ICP81
	Analyte	Recv'd Wt.	Ni	Cu	Co	Pt	Pd	Au	Ag	S
	Units	kg	%	%	%	ppm	ppm	ppm	ppm	%
Method	Analyst	Recvd Wt.	Ni	Cu	Co	Pt	Pd	Au	Ag	S
Sample Description	Units	kg	%	%	%	ppm	ppm	ppm	ppm	%
Sample Description	LOR	0.02	0.005	0.005	0.002	0.005	0.001	0.001	1	0.01
397299		0.75	0.009	<0.005	0.005	<0.005	0.001	<0.001	<1	0.10
397300		0.99	0.044	0.044	0.009	0.005	0.016	0.003	<1	0.26
397301		0.83	0.100	0.218	0.012	0.066	0.078	0.041	<1	1.11
397302		1.15	0.022	0.006	0.003	<0.005	0.002	0.009	<1	1.34
397303		0.72	<0.005	1.325	0.006	0.013	0.009	0.027	4	2.15
397304		1.02	0.012	0.040	0.012	<0.005	0.006	0.014	<1	16.00
397305		0.88	0.007	0.017	0.004	<0.005	<0.001	0.003	<1	2.68
397306		1.01	0.005	0.011	0.005	<0.005	<0.001	0.001	<1	0.14
397307		0.88	0.006	0.005	<0.002	<0.005	0.001	<0.001	<1	0.07
397308		0.70	0.009	0.060	0.006	0.005	0.002	<0.001	<1	1.72
397309		0.91	<0.005	0.005	0.002	<0.005	<0.001	0.008	<1	4.75
397310		0.63	0.007	0.011	0.005	<0.005	<0.001	<0.001	<1	0.26
397311		1.64	0.067	0.853	0.007	0.102	0.062	0.146	2	2.69
397351		2.28	0.008	0.019	0.005	<0.005	<0.001	0.001	<1	0.82
397352		2.18	0.007	0.011	0.005	<0.005	<0.001	<0.001	<1	0.07
397353		1.68	0.007	0.015	0.005	<0.005	<0.001	<0.001	<1	0.71
397354		2.23	<0.005	0.038	0.004	<0.005	<0.001	0.003	<1	2.47
397355		1.65	<0.005	<0.005	<0.002	<0.005	0.001	<0.001	<1	1.82
397356		1.99	0.010	0.040	0.009	<0.005	0.001	0.004	1	8.61
397357		3.24	0.019	0.245	0.158	0.007	0.007	0.025	2	21.0
397358		1.65	0.059	0.763	0.008	0.084	0.047	0.092	3	2.05
397359		1.69	0.048	0.173	0.008	0.021	0.015	0.017	1	0.99
397507		2.70	0.048	0.020	0.005	0.012	0.006	0.005	<1	0.14
397508		1.80	0.042	0.010	0.007	0.009	0.003	0.001	<1	0.08
397528		1.55	0.008	0.017	0.006	<0.005	<0.001	0.001	<1	0.18
397529		2.10	0.012	0.012	0.003	<0.005	<0.001	0.002	1	1.06
397530		1.17	0.010	0.085	0.008	<0.005	<0.001	0.013	<1	2.12
397531		1.85	0.019	0.019	0.005	<0.005	0.001	<0.001	<1	0.95
397532		1.16	0.050	0.007	0.007	<0.005	0.002	<0.001	<1	0.11
397533		1.58	0.013	0.007	0.002	<0.005	<0.001	0.003	<1	0.40
397534		2.06	0.860	0.610	0.033	0.120	0.351	0.043	3	11.25
397535		0.99	0.088	0.193	0.007	0.049	0.088	0.064	2	0.78
397536		1.39	0.277	0.363	0.017	0.053	0.123	0.040	3	2.45
397537		2.13	0.128	0.115	0.011	0.020	0.048	0.017	1	1.06
397538		1.68	0.082	0.049	0.007	0.017	0.032	0.009	1	0.75
397539		1.21	0.010	0.012	0.003	<0.005	0.001	0.003	1	1.24
397540		0.94	0.008	0.008	0.002	<0.005	0.001	0.001	<1	0.48
397636		1.13	0.010	0.005	0.003	<0.005	<0.001	0.001	<1	0.23
397637		2.78	0.006	0.014	0.006	<0.005	<0.001	0.001	1	0.47
397638		3.27	0.006	0.017	0.005	<0.005	<0.001	0.001	<1	0.62



ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

To: CANADIAN ARROW MINES LTD.
BRADY SQUARE
233 BRADY STREET, UNIT #8
SUDBURY ON P3B 4H5

Page: 4 - A
Total # Pages: 4 (A)
Finalized Date: 28-AUG-2008
Account: CNARMN

CERTIFICATE OF ANALYSIS TB08109312

Sample Description	Method	WEI-21	ME-ICP81	ME-ICP81	ME-ICP81	PGM-ICP23	PGM-ICP23	PGM-ICP23	Ag-AA62	ME-ICP81
	Analyte	Recv Wt.	Ni	Cu	Co	Pt	Pd	Au	Ag	S
	Units	kg	%	%	%	ppm	ppm	ppm	ppm	%
Method	Analyst	Recvd Wt.	Ni	Cu	Co	Pt	Pd	Au	Ag	S
Sample Description	Units	kg	%	%	%	ppm	ppm	ppm	ppm	%
Sample Description	LOR	0.02	0.005	0.005	0.002	0.005	0.001	0.001	1	0.01
397647		2.16	0.007	0.005	0.003	<0.005	<0.001	<0.001	<1	0.03
397652		1.62	0.063	0.032	0.005	0.057	0.041	0.057	<1	0.23
397653		2.86	0.058	0.012	0.006	0.011	0.006	0.004	<1	0.07
397654		2.12	0.116	0.069	0.008	0.034	0.026	0.017	<1	0.44
397655		2.52	0.016	0.015	0.004	<0.005	0.002	0.003	<1	0.09
397656		3.39	0.011	0.028	0.004	<0.005	0.002	0.016	1	9.64
397657		2.07	0.012	0.010	0.002	<0.005	<0.001	<0.001	<1	0.38
397658		1.62	0.011	0.019	0.003	<0.005	0.001	0.001	<1	0.46
397659		3.78	0.008	0.035	0.008	<0.005	0.004	0.047	1	13.10
397732		2.92	0.006	0.017	0.005	<0.005	<0.001	0.003	1	0.34
397733		2.14	0.018	0.043	0.008	<0.005	0.002	0.076	2	8.25
397734		2.26	<0.005	0.014	0.005	<0.005	<0.001	0.001	<1	0.32
397735		2.18	0.015	0.013	0.005	<0.005	0.001	0.002	<1	0.70
397736		2.98	0.012	0.021	0.005	<0.005	<0.001	<0.001	<1	1.94
397737		1.43	0.009	0.031	0.006	<0.005	<0.001	0.003	<1	1.84
397738		1.67	0.006	0.048	0.006	<0.005	<0.001	0.006	<1	1.55
397739		2.56	0.008	0.036	0.006	<0.005	<0.001	0.009	1	2.11
397740		1.86	0.013	0.022	0.005	<0.005	0.001	0.002	1	0.85