


**Diamond Drilling
of
CP-10-12, 13, 14, 15
in
4-Corners Area of Kamiskotia Project
in
Jamieson, Robb, Godfrey Townships
on
Claims P3010919, P3011003, P3012747, 3012748
of**

Claim Post Resources Inc.

Report by Hermann Daxl, M.Sc.Minex

31 Dec 2010



Date / Time of Issue: Wed Apr 14 13:17:40 EDT 2010

TOWNSHIP / AREA
ROBBPLAN
G-3968

ADMINISTRATIVE DISTRICTS / DIVISIONS

Mining Division
Land Titles/Registry Division
Ministry of Natural Resources DistrictPorcupine
COCHRANE
TIMMINS


TOPOGRAPHIC

	Land Tenure
<input type="checkbox"/>	Freehold Patent
<input checked="" type="checkbox"/>	Surface And Mining Rights
<input type="checkbox"/>	Surface Rights Only
<input type="checkbox"/>	Mining Rights Only
<input type="checkbox"/>	Leashold Patent
<input type="checkbox"/>	Surface And Mining Rights
<input type="checkbox"/>	Surface Rights Only
<input type="checkbox"/>	Mining Rights Only
<input type="checkbox"/>	Licence of Occupation
<input type="checkbox"/>	Uses Not Specified
<input type="checkbox"/>	Surface And Mining Rights
<input type="checkbox"/>	Surface Rights Only
<input type="checkbox"/>	Mining Rights Only
<input type="checkbox"/>	Railway
<input type="checkbox"/>	Road
<input type="checkbox"/>	Trail
<input type="checkbox"/>	Natural Gas Pipeline
<input type="checkbox"/>	Utilities
<input type="checkbox"/>	Tower
<input type="checkbox"/>	Mine Shaft
<input type="checkbox"/>	Mine Headframe
<input type="checkbox"/>	Contour
<input type="checkbox"/>	CMF, Pt & Pts
<input type="checkbox"/>	Indian Reserve
<input type="checkbox"/>	Provincial Park
<input type="checkbox"/>	Concession, Lot
<input type="checkbox"/>	Township
<input type="checkbox"/>	Administrative Boundaries

MOBERLY	THORBURN	ROBB	CANADIS
BYERS	LOWELAND	MACQUARIE	KIDD
CONE	ROBB	JAMIESON	JESSOP
HASKEY	TURBULL	GODFREY	MOUNTJOY
WHITESIDES	GARDALLIN	BRIXTON	OGDEN
KEEPER	DENTON	THORPELO	

1234	Areas Withdrawn from Deposition
Wam	Mining Add's Withdrawal Types
Ws	Surface And Mining Rights Withdrawn
Wm	Surface Rights Only Withdrawn
Wsm	Mining Rights Only Withdrawn
Wss	Order In Council Withdrawal Types
Wms	Surface And Mining Rights Withdrawn
Wms	Surface Rights Only Withdrawn
Wm	Mining Rights Only Withdrawn


IMPORTANT NOTICE



1: 20,000

Location Map
CP-10-12
CP-10-13
CP-10-14
CP-10-15

CLAIM POST RESOURCES INC.
4-Corners Area, Kamiskotia Project.
Hermann Daxl, M.Sc., 31 Dec 2010



Those wishing to stake mining claims should consult with the Provincial Mining Recorder's Office of the Ministry of Northern Development and Mines for additional information on the status of the lands shown herein. This map is not intended for navigational, survey, or land site determination purposes as the information shown on this map is compiled from various sources. Completeness and accuracy are not guaranteed. Additional information may also be obtained through the local Land Titles or Registry Office, or the Ministry of Natural Resources.

The information shown is derived from digital data available in the Provincial Mining Recorder's Office at the time of downloading from the Ministry of Northern Development and Mines web site.


General Information and Limitations

Contact Information:
Provincial Mining Recorder's Office
West Green Miller Centre 933 Ramsey Lake Road
Sudbury ON P3E 6B5
Home Page: www.mndm.gov.on.ca/MNDM/MINES/LANDS/minmapge.htm

Toll Free: Tel: 1 (888) 415-9845 ext 574
Fax: 1 (877) 670-1444
Map Datum: NAD 83
Projection: UTM (6 degree)

Topographic Data Source: Land Information Ontario
Mining Land Tenure Source: Provincial Mining Recorder's Office

This map may not show unregistered land tenure and interests in land including certain patents, leases, easements, right of ways, flooding rights, tides, or other forms of disposition of rights and interest from the Crown. Also certain land tenure and land uses that restrict or prohibit free entry to stake mining claims may not be illustrated.



Location of CP-10-12 to 15

Claim Post Resources Inc.
4-Corners Area, Kamiskotia Project
Diamond Drilling of Jan - Feb 2010
Hermann Daxl, M.Sc. 31 Dec 2010

Introduction

The present 1300 m of NQ diamond drilling of holes CP-10-12 to 15 at <600m south of Highway 576 about 3km southeast of Kamiskotia Lake, in Jamieson, Robb, and Godfrey Townships, was carried out by Denis Crites Drilling Ltd, Porcupine, for Claim Post Resources Inc, Toronto, on their staked mining claims P3010919, P3011003, P3012747, P3012748, from 21 January to 14 February 2010. Hermann Daxl, M.Sc.Minex, carried out all related field and office work, logged all core, sawed the 241 core samples, and wrote this report. The numerous analyses for many elements were done by Cattarello Assayers Inc., Activation Laboratories Ltd., and ALS Canada Ltd.

The purpose was to follow up on the drilling of 2006-2007 (T-5529 and T-5615), the MAG and IP surveys (T-5092 of 2004, T-5428 of 2006), and the soil surveys (T-5751 and T-5809 of 2006-2008, and the one in progress). The drill holes were layed out to intersect two targets each, which was successful. Even the attitude of ZnV2 - ZnV3 was found to be about 232/63. The discoveries, confirmations, and insight are valuable but no commercial interest is inferred yet.

Access to the drill grounds from Timmins is west via Highway 576, and southward at 250m east of the Robb-Jamieson township line entering the private narrow sand path as outlined on the attached maps, which has now been rebuilt and is too delicate for entering a drill rig next time.

The attached photos, core logs, drill plan, sections including the related CP-06-4 and 5, geochem maps, and lab certificates, are part of this report, and provide convincing details. IP profiles and an excerpt of the MAG map are attached for reference.

Drill hole	Az/Dip	NAD83 UTM 17U	Length	on Claims - %
CP-10-12	302/45	456002 E - 5376708 N	299 m	P3012748 - 12 P3011003 - 88
CP-10-13	220/50	455988 E - 5376632 N	218 m	P3012747 - 10 P3011003 - 90
CP-10-14	052/45	455942 E - 5376465 N	317 m	P3011003 - 19 P3012747 - 81
CP-10-15	147/45	455868 E - 5376528 N	466 m	P3011003 - 60 P3012747 - 29 P3010919 - 11

Total drilled 1300 m

Present Work Details

CP-10-12

From To m m
133.50 - 137.06 3.56 Massive Magnetite Dike :
63.4% Fe, 0.84% TiO₂, 771 ppm V, no Cr Ni Co Nb S.

This dike may have formed from late iron melt, whereas the ilmenite would have crystallized early in gabbro and stayed in place. The drill core is moderately conductive.

From	To	m	m	%Cu	g/t Au	g/t Ag	
111.46	- 111.88	0.42		0.37	0.25	5.40	deuteric gabbro dike (51929)
112.19	- 112.48	0.29		0.01	2.00	3.00	

The attached photos show an aplite dike with assimilated margins and its tension gashes reaching into the deuteric gabbro dike (51652-653), which are crossed by jagged veinlets of gold-bearing pyrite cubes <1cm that also overprint the contact. One can hypothesize that the hydrothermal gold-bearing pyrite therefore came in last, facilitated after the shrinking of the aplite dike, both originating in the partially melted sedimentary rocks below the regional gabbro. In CP-07-7 adjacent younger aplite dikes are barren.

140.00 - 217.00 77.00 local traces of gold in gabbro as quartz-veins are frequent and various pyrite bears gold.

Best values are:

From	To	m	m	%Cu	g/t Au	g/t Ag	
173.40	- 174.49	1.09			0.27		
184.76	- 185.49	0.73			0.37		
206.22	- 206.49	0.27		0.45	0.14	2.90	deuteric gabbro dike (51657)

Considering the local metallogeny, these extensive traces of gold suggest underlying sedimentary rocks that were covered by the gabbro, which would also fit its fine texture. The older medium-grained greenish gabbro could be autoliths. As such one would expect higher gold values below, especially in case the hydrothermal fluids may have been funneled by contacts.

CP-10-13

The gold-bearing shear zone of 285/70 at 455931E-5376623N as per outcrop samples 3012 - 344ppb, 3021 - 288ppb, 3022 - 352ppb Au, and possibly sparse particles in soils (T-5809), was not intersected although nearby.

The quartz-zinc-gold vein ZnV3 previously discovered in CP-06-4 (T-5615) was not intersected here and therefore would not run sub-vertical with its acute core angle of about 20 CA. Its intersection in CP-10-14 fits an attitude of 232/63 which projects it to the showing of ZnV2.

The deep strong IP anomaly (T-5428) at L1150N-1775E was not explained, as ilmenite, probably with hematite, is the same as all over. The anomaly is misplaced or false, the typical problem of IP and pseudo-sections.

CP-10-14

From 29.00 m 0.29 m 0.04 g/t Au 0.20 % Zn

From 94.75 m 0.90 m 0.27 g/t Au 0.61 % Zn :

This thin quartz-calcite-beige sphalerite vein of 30 CA fits a projection from the outcrop ZnV2 at L1150N - 1910E and its adjacent pit, to the 2.92m intersection of ZnV3 of 0.98 g/t Au, 10.15 %Zn at 190.98m in CP-06-4 (see photos in T-5615). The attitude of this ZnV2 to ZnV3 would be about 232/63 (right-hand dip), not allowing for any movement along the adjacent fault which here would cut above the vein, and in CP-06-4 below it as that hole enters under it. Sphalerite here is dull pale beige versus sparkling mid-brown in ZnV3, and darker brown in the other veins.

From 238.30 m 0.26 m 0.04 g/t Au :

This is significant because the geology and also the style of jagged veins of cubic pyrite are the same as some 65m above in CP-06-5 where it intersected 1.3 g/t Au over 4.87 m. Both are well conductive as the cubes are not coated with quartz, unlike at the Highway Gold occurrence in CP-07-7 (T-5631 with photos) where they are coated and therefore do not conduct.

CP-10-15

From m		g/t Au	g/t Ag	% Zn	
243.12	0.24m	0.06	1.90	1.05	4cm q - sl vein 72CA.
245.23	0.27m	0.10	5.00	1.88	10cm q - sl vein 50CA.
296.54	0.41m	0.04	1.00	0.44	10% q - veins 53 CA with sl cusps.
342.12	0.26m	0.32	2.30	6.35	9cm sl - q - cc vein 68CA.
365.31	0.25m	0	0	0.74	2% sl veinlets 85CA.
434.00	0.26m	0.04	2.45	3.71	Cc -q 65CA, 7cm sl center.

These <20cm thick quartz-veins with dull light-beige sphalerite fit a continuation from the similar veins but with medium- to dark-brown sphalerite, intersected at 36.24m in CP-06-4 and others in CP-06-3, and ZnV1 of the main showing about 200m northeast. This consistency suggests that their strike length is extensive. However, the now connected ZnV2 - ZnV3 does not reach CP-06-5 nor CP-10-15, each about 100m away.

Sampling and Analyses

The drill core samples were selected to maximize knowledge. They were kept to under 1kg, which is <50cm of NQ half-core, and were pulverized entirely where important to include all sparse particles. Values of many samples were confirmed with re-runs or multiple pulps. The only variation in sample 51652 is understandable as that core was quartered. Standards and blanks agreed.

Sphalerite this time was light beige and dull, too fine to show its luster (e.g. 57279, 57350, 51668), whereas in previous drilling it was medium-brown or dark-brown, and sparkling. This was realized early enough so that none would have been missed in logging. Sphalerite could also be camouflaged by brown weathering which therefore was also sampled. Sphene could also be taken for sphalerite, however, its habit after ilmenite-hematite is quite revealing. Some was sampled..

As expected, of the wide range of elements analyzed, only gold and zinc values are significant. The highest value for silver was 9 g/t (57311). No platinum, nor palladium, nor rhodium were detected in chosen samples. A deuteritic dike returned 0.37% Cu and 0.25 g/t Au (51929), and another 0.45% Cu and 0.14 g/t Au (51657), but no nickel nor cobalt. The magnetite dike returned 63.4% iron, but only 0.84% TiO₂, 771 ppm vanadium, and no Cr, Ni, Co, Nb, S, despite fusion.

The sometimes recognizable lamination of ilmenite probably is alternating hematite. Sample 57295 with 10% <2mm disseminations returned 5.99 % TiO₂, 227 ppm vanadium, 14 ppm Nb, of the many analyses including iron ore fusion. All values for Cu, Pb, Zn, Ag, S, Au, Pt, Pd, as well as some others of interest, were

entered in the core logs, and marked as to type of analysis per legend on log page 1. Other values were entered only when anomalous or interesting. More details are shown in the attached lab certificates. Highlights are listed on sections as well as on page 1 of the logs.

Geology

The 4-Corners area lies in the regional Kamiskotia Gabbroic Complex, reportedly a tholeiitic intrusive overlain by the Kamiskotia Volcanic Complex of basalt and rhyolite. The several areas of tonalite so far investigated on the Kamiskotia claims (e.g. T-5816) likely are sandstones engulfed and metamorphosed by the gabbro intrusions, and the aplite dikes are offshoots from their local melt.

The Ti-rich fine-grained dark gabbro of the drill area causes local magnetic highs and strong IP-chargeability anomalies due to ubiquitous 2 - 7% laminated ilmenite-hematite with local magnetite intergrowth. Few remnants of older green medium-grained variably epidotized gabbro occur throughout and also contain similar ilmenite. Sphene after ilmenite indicates proximity to felsic rocks, as the necessary silica was assimilated by the congealing gabbro. Alteration to sphene or leucoxene is locally found near faults and quartz-veins.

Metallogeny

Although no gold values were found in the sandstone protoliths, except in quartz veins near their edge, it seems that they are the source of the several gold occurrences discovered so far, namely quartz-veins with gold-bearing sphalerite, or with gold-bearing chalcopyrite, or with gold-bearing <1cm pyrite cubes that also occur as jagged veinlets of cubes near a gabbro-tonalite contact. This has been discussed and illustrated in previous drill reports (T-5529, T-5615, T-5631, tonalite T-5816) and the present intersections agree with it.

The system of <1m thick quartz-veins with gold-bearing sphalerite strikes SW with a steep NW dip, over at least 300m in the area so far drilled at the 4-Corners, and seems quite predictable. Veins with gold-bearing pyrite so far have been <1cm, plus associated pockets, and except for CP-10-12 are quite rare. Rare <5cm chalcopyrite patches in quartz-veins occur in CP-10-6.

The present only two low copper values are magmatic in thin deuteritic gabbro dikes in CP-10-12. The traces of gold could be a coincidence.

The magnetite dike now discovered in CP-10-12 seems to stem from cumulates. Where quite pure (sample 51938) it contains 63.40 % iron but only 0.84% TiO₂, and

771 ppm vanadium, and no other values. Ilmenite-hematite crystallizes very early, whereas iron not consumed by it or by mafic minerals can be enough to form liquid cumulates. Note that laminated ilmenite-hematite cumulates can form where titanium is very abundant, as in Lac Allard, Quebec.

Geophysics

The ground MAG map (T-5428) shows abrupt extreme magnetic low-highs at L1375N - 1780E and L1300N - 1570E, with differences in the 5m readings of 10000 and 12000 nT respectively, over only 25m. The latter deflects the compass from 172 to 113 az. The likely cause is a sub-cropping massive magnetite dike as intersected in CP-10-12, possibly with remanent magnetism, or as edge effects.

The drill core of that 3.56m magnetite dike intersection at 50CA, 87m below L1300N - 1640E is a moderate conductor, but makes no chargeability anomaly. The IP conductivity pseudo-section shows a conductor at that depth rising along CP-10-12, which would be across the logical attitude of the dike. Although this may be the conductor, pseudo-sections allow too many ways of interpretation for drilling. Further, the extreme low-high surface MAG anomalies show no matching conductivity, nor chargeability anomalies which instead usually match outcrops of gabbro with its ubiquitous laminated ilmenite-hematite grains that act like capacitors.

The outcrops around L1300N - L1600E show no chargeability on profile L1300N and need to be checked whether the titanium mineral is sphene which indicates silicification 120m below, where traces of gold occur over 77m in CP-10-12 from 140 to 217m. The wider MAG high here then would also need to be attributed to the magnetite dike and its infiltrations. However, profile L1600E across this same spot shows IP highs like at other outcrops. Again IP proves to be misleading.

At L1150N - 1750 to 1800E the deep abrupt high chargeability anomaly centering at a depth of 80m was cut exactly by CP-10-13 but only the usual ubiquitous ilmenite disseminations were encountered. If real at all, there seems to be no way to locate the cause of an IP anomaly.

CP-10-14 and CP-10-15 were both drilled in only 9m thick overburden with only 10 - 60 cm humus over clay. Despite the same gabbro with ubiquitous ilmenite that makes strong chargeability and high resistivity anomalies at outcrops, here the profiles are monotonous and flat. This alone proves that IP over clay is useless, and of course the usual 2 - 7 % disseminated ilmenite-hematite makes it misleading elsewhere.

At best one can judge the depth of thin overburden with IP as around L2000E above CP-10-15, but this can even be surmised from the start of the eastward

slope there. The ground MAG at 5m intervals is more effective for that anywhere.

MaxMin could detect larger bodies of gold-bearing pyrite where conductive like in CP-06-5, however, it is not conductive in CP-07-7 (T-5631 with photos) where the cubes are coated with quartz.

Soil sampling

The previous orientation study of mainly enriched soil by aqua regia - mass spectrometry shows that zinc-cadmium anomalies correspond to known quartz-zinc-gold veins, even if none was intersected by CP-10-12 under the small cadmium anomaly. CP-10-15 intersected few such veins under the zinc-cadmium anomaly in the swamp that wraps around the southwest outcrop area where it may have been spread by swamp water.

The recent small study of decayed vegetation 0 - 6 cm below surface by neutron activation analyses has already had even more success, with higher values and less chance for error. Sample 693 of 4190 ppm Zn, 69.6 ppm Cd, and 13 ppb Au, is 20m down-slope from ZnV1, and 694 is 25m into the swamp (please see attached sample and element maps). The much smaller value of sample 695 at the base of that slope minimizes the risk of displaced anomalies. The gold associated with the sphalerite also shows.

Gold values <0.35 g/t were found in a small outcropping shear zone trending 285/70 but were not intersected by CP-10-13. The surrounding gold anomalies, could not be repeated by the previous method, but showed again in decay samples 687 and 688. It appears that gold by aqua regia - mass spectrometry is not reliable, and that possibly gold adheres or even accumulates in the tube and gets released at random. A possible coincidence of sparse particles is still under review, as these previous samples were sand to clay. Decay sample 682 actually is close to a minor gold value in CP-10-12 and 691 to values in CP-10-5.

At the Highway Gold showing 300 m north of highway 576 the decay sample 689 over a pile of soil stripped from the showing only 6 years ago returned 1960 ppb Au. It may confirm the hypothesis that gold is easily mobilized from weathering pyrite and migrates to the surface where water evaporates, and where it deposits like efflorescence on a wall. So much gold could not have come from inside decayed leaves. Analyses from the Dayton showing indicate that some gold also goes into the decayed maze of tiny rootlets, compared with the <250 micron fraction rubbed off from them. Decay samples also returned the highest value of 108 ppb Au 60m above the McEnaney gold-bearing quartz-vein.

Decay samples are from the top 6cm of humus, after scraping off loose debris and green vegetation, namely the maze of rootlets and decayed plants or leaves with attached efflorescence, but still without soil or minerals. Values are

much higher than in the sand to clay from 10 - 20cm below the humus, even where enriched. They are more convenient to collect, to sieve to <250 micron, and to analyze packed in small vials to about 1g, by neutron activation down to the <2 ppb limit. This sampling worked also well for zinc, and cadmium by aqua regia - ICP-OES. The suitability for other elements still needs testing, but so far copper under 10m of swamp gave no anomaly. Sparse particle effects like in soils are unlikely as a possible 10x10x1 micron gold flake is only 1 ppb per 1 g.

Conclusions and Recommendations

Much has been learned and confirmed in the present drilling. A large area with traces of gold, as well as a magnetite dike have been discovered in CP-10-12. The best intersection so far, ZnV3 in CP-06-4, can be projected through CP-10-14 to the outcrop of ZnV2, resulting in an attitude not too different from the other set of such veins which, however, is more predictable and has been extended. Sphalerite this time was found dull pale-beige, not glittering medium- to dark-brown, and could easily be missed.

The present work has again confirmed how inadequate IP is especially for this type of mineralization and overburden. The veins are too extensive and sparse to follow with drilling. Sampling the enriched soil horizon works for zinc and associated cadmium, however, sampling the decayed vegetation and leaves to 6 cm depth from surface and analyzing them by neutron activation will make anomalies very conspicuous also for gold as well as for zinc and cadmium.

The two MAG extremes could be excavated, although it may all be the same quite pure magnetite. Deep holes to probe for better gold values under CP-10-12, or for the depth of ZnV3, is too risky until these systems are better understood.


This practically leaves only the sampling of the decayed vegetation for exploration of the wider vicinity, starting with the higher ground before the swamps. No grid is necessary because choosing the right sample should not be restricted by a grid. GPS location and marking the spot suffice. Only special circumstances need to be noted. Anomalies need to be further sampled and statistical highs discarded. True anomalies are as rare as showings. Meticulous work is therefore absolutely necessary.

Respectfully submitted,




Timmins, 31 Dec 2010

Hermann Daxl, M.Sc.Minex



CP-10-12 : 111.46 - 111.88 = 51929 = 0.25 g/t Au / 0.42 m
 0.37 % Cu
 5.4 g/t Ag 1.5% S







CP-10-12 : 112.19 - 112.48m = 51931 + 51652 = 2.0 g/t Au, 3.0 g/t Ag / 0.29m



Pyrite cubes are not coated here, therefore the veinlets conduct moderately.





Chalcopyrite and pyrite infiltration into dike 51929.



CP-10-12 : 174.25 - 174.49 = 57381 = 0.56 g/t Au / 0.24 m

CLAIM POST RESOURCES INC., Kamiskotia Project

4-Corners Grid (L2000E is 35 az, Mag decl. 11 W)

Grid Location (m): L 1300 N - 1745 E

Map: G-3986 Township: JAMIESON P 3012748 - 12%
G-3968 ROBB Twp. Claims: P 3011003 - 88%

UTM NAD 83 - Elevation 2 m above CP-06-1, 2.

17U 045 6002 E - 5376708 N

DDH Direction (azimuth) / Dip (plunge): 302/45 degrees

Hole Length: 299 m Core Diameter: NQ - 47 mm

Casing Length: 6 m Overburden Thickness: 2 m

Casing left in hole and capped, marked by wood post.

Other: Waterseam at 154 m.

Core stored in 70 trays at: 6076 King St., Porcupine, ON.

Water from CP-06-1 but takes good suction pump, or submersible.

108 Samples (Continuous sawed half core): 51652 - 657,

51909 - 932, 51934 - 959, 51961 - 982, 51984 - 998,

57380 - 394.

Highlights:

133.50 - 137.06 3.56 Massive Magnetite Dike,
moderate conductor, 63.4% Fe, 0.84% TiO₂, 771 ppm V,
no Cr Ni Co Nb S.

From	To	m	m	%Cu	g/t Au	g/t Ag	
111.46	- 111.88	0.42	0.37	0.25	5.40		photos

112.19	- 112.48	0.29	0.01	2.00	3.00		photos
--------	----------	------	------	------	------	--	--------

173.40	- 174.49	1.09		0.27			
--------	----------	------	--	------	--	--	--

184.76	- 185.49	0.73		0.37			
--------	----------	------	--	------	--	--	--

140.00 - 217.00 77.00 further traces of gold in gabbro
as quartz-veins are frequent and various pyrite bears gold.

206.22	- 206.49	0.27	0.45	0.14	2.90		
--------	----------	------	------	------	------	--	--

LOG of DDH CP-10-12

Page 1 of 13

Drilling Started: 21 JAN 2010 Finished: 26 JAN 2010

Drilled by Denis Crites Drilling Ltd., Porcupine.

Set-up checked by: Daxl Hole stopped by: Daxl

Logged by: H. Daxl, M.Sc.

Submitted and Signed:

Dip-Acid Tests:	0 m	45°	200 m	41°
	32 m	40°	299 m	41°
	101 m	40°		

Trace: 226 m horizontal, 195 m vertical

Legend:

H Mohs' hardness, as measure of alteration.

M5 Magnetic like magnetite, M0 = nonmagnetic.

CA Degrees to core axis.

F5 Fizz like calcite as reaction to cold 10% HCl.

RQD % core length longer than 2.5 x diam, >12cm.

Analyses

by Cattarello, Actlabs, or ALS. Pulverized most samples entirely.

Details on certificates and logs. A = Aqua regia - ICP,

F = 30 g Fire assay, N = 30 g Neutron activation,

T = 4-acid near Total - ICP W = Whole rock fusion.

CP-10-12

Box night shift 23.1. | Box 22.1. 2010
 Box 23.1.10

BOX	FROM m
1	3.00 (Carry to 6 m)
2	7.15
3	11.42
4	15.58
5	19.80
6	24.00
7	28.18
8	32.42
9	36.50
10	40.57
11	44.50
12	48.68
13	52.83
14	57.09
15	61.42
16	65.61 low 50 cm
17	70.07
18	74.16
19	78.52
20	82.82
21	87.13
22	91.40
23	95.57
24	99.85
25	104.10 ground 93 cm
26	108.90
27	112.84
28	117.00
29	121.20
30	125.50

BOX	FROM m	in
31	129.70	
32	133.77	
33	138.00	
34	142.22	
35	146.40	
36	150.65	
37	155.00	
38	159.45	
39	163.65	
40	168.03	
41	172.32	
42	176.63	
43	180.95	
44	185.00	
45	189.28	
46	193.56	
47	197.80	
48	201.95	
49	206.00	
50	210.20	
51	214.44	
52	218.58	
53	222.70	
54	227.00	
55	231.35	
56	235.56	
57	239.71	
58	244.05	
59	248.20	
60	252.46	
61	256.47	
62	260.76	
63	265.25	

269.43

273.95

278.16

282.44

286.80

290.75

294.94 -

- 299.00 END

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-12 Page 2

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-12 Page 3

FROM - TO m	ROCK UNIT	S A M P L E			%	%	%	g/t	%	g/t	g/t	g/t	OTHERS - % - g/t
		NUMBER	FROM - TO m	LENGTH	Cu	Pb	Zn	Ag	S	Au	Au	Au	
		51911	Chloritic fine deuteritic dike 5 CA with some 5% magnetic ilmenite and 5% quartz-calcite stringer. 60% wallrock.	16.16 - 16.57	0.41	W 0.01	W 0	N 0.03	N 0	N 0	F 0		F 0 Pt, F 0 Pd, N, Wt 51911 Whole Rock Fusion: % : 43.17 SiO ₂ , 19.78 Fe ₂ O ₃ (T), 11.53 Al ₂ O ₃ , 5.89 MgO 6.77 CaO, 3.31 TiO ₂ 1.01 Na ₂ O, 0.25 MnO 0.04 K ₂ O, 0.21 P ₂ O ₅ 6.80 LOI. ppm: 809 V 60 Ni 9 Nb 68 Co
23.00 - - 32.90	FINE GABBRO - ILMENITE	mFGil	Medium-gray fine-grained melagabbro. 4% ilmenite. H=6. Quite homogeneous.										
			Weakly magnetic, plagioclase fizzes weakly to strongly downhole. RQD 98%. Barren. Abrupt transition downhole as ilmenite altered to sphene due to quartz-veining 2 m below.										
32.90 - - 44.65	FINE GABBRO - SPHENE	FGsn	As before but 5% sphene instead of ilmenite. H = 5-6. Few 1 cm quartz-chlorite-calcite veins around abrupt transition below. Rhyolitic xenolith at 43 m. Nonmagnetic. Fizz turns strong downhole. RQD 90%. Barren.										
		51912	4 cm quartz-albite? - greenish plagi- close vein 35 CA with minor pyrite cubes and trace chalcopyrite. No halo other than zone of sphene.	34.44 - 34.64	0.20		N 0.01	N 0	N 0.03	F 0.07	N	N 2.3 ppm U. F 0 Pt, F 0 Pd	
		51913	10% similar vein 30 CA parallel to above vein and to joint with rustbrown weathering. Trace pyrite cubes.	34.88 - 35.18	0.30		N 0.01	N 0	N 0		N		

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-12 Page 4

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-12 Page 5

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-12 Page 6

FROM - TO m	ROCK UNIT	S A M P L E			%	%	%	g/t	%	g/t	g/t	OTHERS - % - g/t
		NUMBER	FROM - TO m	LENGTH	Cu	Pb	Zn	Ag	S	Au	Au	
	51920 2 cm quartz-vein 25 CA with shear over 10 cm uphole with minor weathered plating	51920	93.80 - 94.20	0.40				N 0.01	N 0	N 0.01	F 0.01	N F O Pt, F O Pd
F18	94.40 FAULT 18 CA dive gouge washed out, subparallel to Quartz vein above. Quartz-calcite Breccia fragments up to and included in 51920.											
109.40 -	APLITE DIKE - PYRITE-MAGNETITE MARGIN											
-112.60	Probably not a xenolith because 2 cm quartz-aplite dk. albite tension gashes thin outward from center and end at contact, although contacts are diffuse. The assimilation resemblance seems due to infiltration of very fine deuteritic gabbro which bears some chalcopyrite. Pyrite and gold is later hydrothermal. Moderate Conductor as cubes tend without coating. Pink apliteitic to gray with dark crackles, H=7, aplite dike. Up-hole contact 15 CA.	51921	108.91 - 109.26	0.35 ↓				N 0.01	N 0	N 0	F 0.01	N F O Pt, F O Pd
15		51922	109.26 - 109.48	0.22				N 0	N 0	N 0	F 0	N F O Pt, F O Pd
		51923	109.48 - 109.83	0.35				N 0	N 0	N 0	F 0	N N 2.43% Na, N 6.6 ppm Th, F O Pt, F O Pd
		51924	109.83 - 110.19	0.36				N 0	N 0	N 0.05	F 0.06	N N 29 ppm As, F O Pt, F O Pd
	Else nonmagnetic, no fizz, RQD 90%.	51925	110.19 - 110.44	0.25				N 0.01	N 0	N 0	F 0.01	N F O Pt, F O Pd
	109.83-110.16 medium-grained gabbro with sphene, unlike the wallrock, is a xenolith.	51926	110.44 - 110.88	0.44				N 0	N 0	N 0	F 0.01	N N 6.6 ppm Th, F O Pt, F O Pd
dent dk. 5% cp	111.50 - 111.80 Deuteric very fine-grained gabbro dike, locally chloritic with assimilating pelitic wallrock irregular wavy glancing. 5% interstitial chalcopyrite. Groupings of <5 mm pyrite cubes at contacts. Younger than aplite but older than pyrite and even gabbro.	51927	110.88 - 111.18	0.30				N 0	N 0	N 0	F 0.02	N N 6.4 ppm Th, F O Pt, F O Pd

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-12 Page 7

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-12 Page 8

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-12 Page 9

FROM - TO m	ROCK UNIT	S A M P L E			%	%	%	g/t	%	g/t	g/t	g/t	OTHERS - % - g/t
		NUMBER	FROM - TO m	LENGTH	Cu	Pb	Zn	Ag	S	Au	Au	Au	
Gsn.vqpy	Magnetite infiltration 40° CA to 142 m and bands at 147.60-149.55 parallel 50 CA.												
vq py	140.50 - 151.00 QUARTZ-VEINS WITH PYRITE 5% gray-white-clear aplomorphic quartz veins locally with much fine pyrite and abrupt beige halo where only sphene still visible, 25-50 CA subparallel. No fizz. Disappering below.												
	Else non-magnetic, rare fizz except halo to 141 m. RQD 95%. 5-10% sphene throughout but with magnetite only at 151-155 as 5 mm clusters.												
	Core fitted continued to 156 m, also 162-165, and oriented.												
51940	4% Quartz vein, 20% magnetite infiltr.	51940	140.42 - 140.64	0.22	N	N	N	N	O	F O			N F O Pt, F O Pd.
51941	7% pyrite, 10% quartz-veins, 10% mt	51941	140.64 - 140.88	0.24	N	N	N	N	0.06	F O, 0.07			N N 25.50% Fe, 62 ppm Sc, N 3.2 ppm U
51942	1% pyrite, 8% magnetite.	51942	141.46 - 141.83	0.37	N 0.01	N	N	N	O				N N 155 ppm As, F O Pt, F O Pd
51943	3% pyrite, 10% quartz-veins, 3% mt	51943	141.83 - 142.22	0.39	N	N	N	N	0.04	F O, 0.03			N N 21% Fe
51944	7% pyrite, 5% quartz-veins.	51944	142.22 - 142.61	0.39	N	0.01	N	N	0.05	F O, 0.04			N F O Pt, F O Pd
51945	2% pyrite, sheared.	51945	143.00 - 143.26	0.26	N	0.01	N	N	O	F O, 0.01			N N 131 ppm As, F O Pt, F O Pd
51946	Quartz-py breccia vein 30 CA, parallel shear.	51946	143.26 - 143.52	0.26	N	O	N	N	0.12	F O, 0.09			N F O Pt, F O Pd
51947	5% quartz-veins	51947	145.17 - 145.52	0.35	N	O	N	N	O				N N 78 ppm As, F O Pt, F O Pd.
51948	20% quartz-veins incl. sharp halo.	51948	146.11 - 146.40	0.29	N	O	N	N	O				N N 2% Na
51949	5% quartz-veins with minor pyrite.	51949	146.68 - 146.92	0.24	N	O	N	N	O				N N
51950	3% quartz-veins, 1% pyrite	51950	146.92 - 147.23	0.31	N	0.02	N	N	O				N N 2.15% Na
51951	10% quartz-vein, 5% pyrite, 10% mt,	51951	148.76 - 149.00	0.24	N	0.01	N	N	0.09	F O, 0.10			N N 22.6% Fe, F O Pt, F O Pd
51952	3% quartz-vein, trace pyrite disseminated	51952	149.00 - 149.27	0.27	N	0.02	N	N	O				N N 2.16% Na
51953	15% quartz-vein incl. halo, 1% pyrite	51953	149.27 - 149.62	0.35	N	O	N	N	O				N N

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-12 Page 10

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-12 Page 11

FROM - TO m	ROCK UNIT	S A M P L E			%	%	%	g/t	g/t	g/t	OTHERS - % - g/t
		NUMBER	FROM - TO m	LENGTH	Cu	Pb	Zn	Ag	S	Au	
	51655 3% qv < 5mm, 4% py < 3mm, 4mm cp.	51656	185.00 - 185.25	0.25						F 0.69	F 0.68
		51994	185.25 - 185.49	0.24			N O	N O		N 0.28	F 0.24
	51970 15% q albite, 1% < 2mm py cubes	51995	185.49 - 185.82	0.33			N 0.02	N O		N 0	F 0
		51996	186.37 - 186.87	0.50			N 0.02	N O		N 0	
	51978 2cm qv, ankerite? selvage, barren, 24CA	51997	191.00 - 191.39	0.39			N O	N O		N 0	
		51977	191.39 - 191.74	0.35			N O	N O		N 0.32	F 0.24
	51657 Assimilating xenoliths, felsic with 1mm pyrite cubes, and mafic with 1cm magnetite pat- ches and which scavenged much chalcopyrite. All in a fine deuteritic dike with sphene 35CA.	51978	191.74 - 192.07	0.33			N O	N O		N 0	F 0.01
		57391	193.30 - 193.56	0.26						F 0.30	
		51979	197.34 - 197.56	0.22			N 0.02	N O		N 0	F 0
		51657	206.22 - 206.49	0.27	T 0.41 W 0.43	T 0 W 0.02	E 2.4	1.5		F 0.15	F 0.13
	51998 30% quartz-albite veins 15 CA, rare py < 1mm.	51998	207.33 - 207.63	0.30			N 0.01	N O		N 0	
	51980 few 8mm py. 25% gray qv with fine py.	51980	216.00 - 216.43	0.43			N 0.02	N O		N 0.04	F 0.02
	51981 25% albite-quartz vein 2cm, barren.	51981	216.43 - 216.85	0.42			N O	N O		N 0	
	51982 25%, clear quartz vein ~35° to above vein A similar vein at 221m.	51982	216.85 - 217.25	0.40			N O	N O		N 0	
		51983	STAND. DREAS 13.6	✓							
	51984 Quartz-vein clear with much chalcopyrite parallel to core, glanced sample.	51984	223.08 - 223.30	0.22	T 0.12 T 0.01	N O	N 1.0	0.34	N 0.01	F 0.02	N, T T 219 ppm V, F 0.01, F 0.02
		57392	224.65 - 224.94	0.29						F 0.02	
227.00 - - 234.50	FINE GABBRO - ILMENITE - MAGNETIC	57393	224.94 - 225.30	0.36						F 0	F 0 Pt, F 0 Pd
	Dark-gray fine-grained meta-gabbro, mFG il 2-5% fine patches of magnetic ilmenite, H = 6. ~1% < 2 cm quartz-calcite veins.	57394	226.69 - 227.00	0.31						F 0.01	F 0 Pt, F 0 Pd
		57395	TEST DAX 1	✓							
	Moderately magnetic, moderate size, Rd 98%, else barren. Intransitions.										*W+ 51657: Whole Rock Fusion w/ ppm:
	51985 1% chalcopyrite grouping in quartz-calcite, all in sample.	51985	229.85 - 229.70	0.15	T 0.06 T 0.01	N 0.02	N O	0.17	N 0	F 0	26.20 SiO ₂ , 29.02 Fe ₂ O ₃ 9 Nb
										(206 ppm V, 0 Pt, 0 Pd)	8.45 Al ₂ O ₃ , 5.16 MgO 80 Ni
234.50 - - 246.00	GREEN GABBRO - ILMENITE - MAGNETIC		173.40 - 174.49	1.09							10.36 CaO, 1.38 TiO ₂ 80 Cr
	mGG il 2mm green plagioclase lathes and few such.		184.76 - 185.49	0.73							0.07 Na ₂ O, 0.21 MnO 454 V
											0.51 K ₂ O, 0.36 P ₂ O ₅ 77 Co
											14.04 LOI, 41 ppm Ge 41 Y

GRADE : 0.27 g/t Au / 1.09m

GRADE : 0.37 g/t Au / 0.73m

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-12 Page 12

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-12 Page 13 (END)

FROM - TO m	ROCK UNIT	S A M P L E			%	%	%	g/t	%	g/t	g/t	g/t	OTHERS -% -g/t
		NUMBER	FROM - TO m	LENGTH	Cu	Pb	Zn	Ag	S	Au	Au	Au	
	Then 80% due to veins and slickensides near 20 CA, Barren.												
51988	10% magnetite infiltration cusp <2 cm with chlorite and trace epidote and pyrite <1mm. 2% quartz-calcite veinlets.	51988	271.54 - 271.86	0.32		N 0.01	N 0			N 0	F 0		N N Lanthanides, F O Pt, F O Pd
51989	5cm clear quartz-vein 20 CA, albite? Selvage, minor pyrite-sericitic halo.	51989	273.95 - 274.23	0.28		N 0	N 0			N 0.09	F 0.12		N F O Pt, F O Pd
51990	3 cm such QV, no pyrite but parallel fracture with q-calcite haloes, separate 3cm magnetite seam 70 CA perpendicular to QV. Further such QV at 283.70.	51990	282.60 - 283.10	0.50		N 0.01	N 0			N 0.01	F 0.01		N N 20 ppm W, F O Pt, F O Pd
51991	20% quartz-calcite-dolomite veining 25 CA, continues to 292.80	51991	292.00 - 292.25	0.25		N 0	N 0			N 0	F 0		N F O Pt, F O Pd.
299.00m	END OF HOLE												
ADDITIONAL SAMPLING - See also previous on page 10													
57381	2% quartz veinlets <3 mm, trace pyrite cubes <4mm.	57381	174.25 - 174.49	0.24						F 0.56			F O Pt, F O Pd
57382	barren.	57382	174.49 - 174.74	0.25						F 0.02			F O Pt, F O Pd
57383	5% quartz-veinlets <3 mm with very minor pyrite	57383	174.74 - 175.02	0.28						F 0.03			F O Pt, F O Pd
57384	5% quartz-veinlets <3 mm with very minor pyrite	57384	175.02 - 175.30	0.28						F 0.01			F O Pt, F O Pd
57385	5% barren quartz-veinlets <5 mm. 10% lighter.	57385	175.30 - 175.64	0.34						F 0			F O Pt, F O Pd
57386	1% barren quartz-veinlets. 50% lighter.	57386	175.64 - 176.00	0.36						F 0.01			F O Pt, F O Pd
57387	1/2 barren quartz-veinlets. Rare pyrite <1mm.	57387	176.00 - 176.30	0.30						F 0.01			F O Pt, F O Pd
57388	Trace <1mm pyrite cube disseminations.	57388	176.80 - 177.00	0.20						F 0.04			F O Pt, F O Pd
57389	Rare trace <1mm pyrite cubes.	57389	177.00 - 177.26	0.26						F 0.01			F O Pt, F O Pd
57390	Barren.	57390	177.26 - 177.55	0.29						F 0			F O Pt, F O Pd

CLAIM POST RESOURCES INC., Kamiskotia Project

4-Corners Grid (L2000E is 35 az, Mag decl.11 W)

Grid Location (m): L 1231 N - 1784 E

Map: G-3986 Township: JAMIESON ROBB Claims: P 3012747 - 10%
G-3968

UTM NAD 83 - Elevation 2m above CP-06-1,2; Level CP-06-5,6.
17U 0455988 E - 5376632 N

DDH Direction (azimuth) / Dip (plunge): 220/50 degrees

Hole Length: 218 m Core Diameter: NQ - 47 mm

Casing Length: 12 m Overburden Thickness: 7 m

Casing left in hole and capped, marked by wood post.

Other: 45 m casing broken off down void? at first 45° attempt.

Core stored in 49 trays at: 6076 King St., Porcupine, ON.

Water from CP-06-5, submersible, enough for a fire engine.

17 Samples (Continuous sawed half core):

51658-660, 57252-257, 57259-266.

Highlights:

Gold zone 285/70 at 455931E-5376623N as per outcrop and soils (T-5809), was not intersected although nearby. Outcrop ppb Au: #3012 - 344, 3021 - 288, 3022 - 352 ppb.

ZnV3 was not intersected and therefore is unlikely to run sub-vertical with its acute angle to CP-06-4 (T-5615).

The strong deep IP anomaly (T-5428) at L1150N-1775E was not intersected unless due to ubiquitous laminated ilmenite-hematite, which would act like a capacitor.

LOG of DDH CP-10-13

Page 1 of 8

Drilling Started: 26 JAN 2010 Finished: 1 FEB 2010

Drilled by Denis Crites Drilling Ltd., Porcupine.

Set-up checked by: Daxl Hole stopped by: Daxl

Logged by: H. Daxl, M.Sc.

Submitted and Signed: 

Dip-Acid Tests:	0 m	50°	188 m	44°
	30 m	45°	200 m	45°
	101 m	44°		

Trace: 154 m horizontal, 153 m vertical.

Crosses: L1150N - 1769 E.

ENDS: L1075N - 1768 E.

Legend:

H Mohs' hardness, as measure of alteration.

M5 Magnetic like magnetite, M0 = nonmagnetic.

CA Degrees to core axis.

F5 Fizz like calcite as reaction to cold 10% HCl.

RQD % core length longer than 2.5 x diam, >12cm.

Analyses

by Cattarello, Actlabs, or ALS. Pulverized most samples entirely.

Details on certificates and logs. A = Aqua regia - ICP,

F = 30 g Fire assay, N = 30 g Neutron activation,

T = 4-acid near Total - ICP W = Whole rock fusion.

CP-10-13 (casing 12 m, 2 m into bedrock)

BOX	FROM m -	BOX	FROM m -
1	11.00	32	141.73
2	15.60	33	145.88
3	19.82	34	150.17
4	24.08	35	154.40
5	28.25	36	158.66
6	32.48	37	162.92
7	36.80	38	167.10
8	41.00	39	171.45
9	45.36	40	175.65
10	49.67	41	179.73
11	53.84	42	184.06
12	57.62	43	188.23
13	61.45	44	192.45
14	65.55	45	196.75
15	69.70	46	201.00
16	74.00	47	205.32
17	78.29	48	209.39
18	82.45	49	213.85 -
19	86.66	1, 2, NIGHT	- 218.00 Eoff
20	90.92		
21	95.06		
22	99.32		
23	103.58		
24	107.79		
25	112.10		
26	116.18		
27	120.40		
28	124.73		
29	128.90		
30	133.26		
31	137.43		

1 28.1.10 PM Back off 28.1. AM

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-13 Page 2

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-13

Page 3

FROM - TO m	ROCK UNIT	S A M P L E			%	%	%	g/t	%	g/t	g/t	OTHERS - % - g/t
		NUMBER	FROM - TO m	LENGTH	Cu	Pb	Zn	Ag	S	Au	Au	Au
36.60 - m GG	In dark-gray mass, H=6, <15% pyrrhotite veilings and stringers H=7 especially in margin. Inconspicuous <3% ilmenite <1mm.											
	Weakly magnetic, no fizz, RQD 98% except at 41 m. Barren. Abrupt contacts. Older.											
	40.60 - 41.00 MINOR FAULT ? 10 CA. Minor gouge?											
49.85 - - 55.77	FINE GABBRO - YOUNGER											
F6.y	Dark-gray, very fine-grained, <3% ilmenite hardly visible, H=6-3 downhole. Few xenoliths from above.											
	Weakly magnetic to 52 m. Moderate fizz disappears downhole, RQD 98% to 53 m. Barren. Lower contact 48 CA due to shear.											
F45	54.50 - 55.60 MAJOR FAULT ZONE WITH SHEAR 45CA. Several planes with fault gouge, RQD 0%. Ilmenite altered to leucosene.											
55.77 - - 62.30	TONALITE DIKE											
T	Medium-gray, diffusely fine-grained, 20% mafics, H=6-7, locally high line.											
	Nonmagnetic, minor local fizz, RQD 90%. Barren. Lower contact 50 CA. <5cm b-halo.											
57253	251. barren quartz-veins shear 50 CA.	57253	59.18 - 59.63	0.45			N	O	N	O	N	N 5 ppb Ir, N 4.2 ppm Th.

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-13 Page 4

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-13 Page 5

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-13 Page 6

FROM - TO m	ROCK UNIT	S A M P L E			% Cu	% Pb	% Zn	% Ag	% S	g/t Au	g/t Au	g/t Au	OTHERS - % - g/t
		NUMBER	FROM - TO m	LENGTH									
	Nonmagnetic, minor fiss. RQD 96%. ~1% pyrite cubes <2mm. Transitional contacts.												
	57261 30% calcite-quartz vein 10 CA, 1% <2mm pyrite cubes disseminated throughout.	57261	144.75 - 145.16	0.41	N 0	N 0	N 0	N 0	N 0	N 0	N 0	N 0	N 9% Ca
	57262 15% <1cm quartz-calcite veins ~ 90 CA. Trace pyrite.	57262	152.36 - 152.83	0.47	N 0.02	N 0	N 0	N 0	N 0	N 0	N 0	N 0	N 5% Ca
156.00 - -168.00	MELAGABBRO m Gmel												
	Dark gray, 5-20% fine interstitial white plagioclase. H=6-7. 1% epidote veinlets with halos. 2-5% ilmenite hardly visible. weak magnetism disappears downhole. No fiss. RQD 96%. Abrupt interfingering below.												
168.00 - -193.50	GABBRO GG												
	Medium-gray, 40% 2mm greenish plagioclase H = 6-7 seldom chloritic. 2-5% ilmenite not conspicuous. Rare epidote stringers. Nonmagnetic. No fiss. RQD 96%. Trace <2mm pyrite cubes. Transition below.												
	57263 1% pyrite cubes <2mm as clusters and disseminations. 3% ilmenite <1mm.	57263	183.42 - 183.85	0.43	W 0	W 0	W 0.01	N 0	W 0.4	N 0	F 0	N W	W + 57263 IRON ORE FUSION-XRF % : 45.9 SiO ₂ 12.84 FeO 13.10 Al ₂ O ₃ 4.47 MgO 7.03 CaO 3.78 TiO ₂ 3.18 Na ₂ O 0.20 Mn 0.17 K ₂ O 0.10 P W ppm: 270 V, 70 Co, 0 Cr, 0 Ni, N W N 31 ppm Sc, F 0 Pt, P, O, Pd.

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-13 Page 7

FROM - TO m	ROCK UNIT	SAMPLE			% Cu	% Pb	% Zn	% Ag	% S	g/t Au	g/t Au	g/t Au	OTHERS - % - g/t
		NUMBER	FROM - TO m	LENGTH									
193.50 - - 199.00	FINE MELAGABBRO												
		Dark gray, very fine-grained, melanocratic. FG mel H=5-6. 3% ilmenite. Nonmagnetic, minor to moderate fizz. RQD 98%. Barren.											
199.00 - - 207.35	FINE GABBRO - ILMENITE												
		Medium gray. Beige fine plagioclase. H=5-6. FG il 3% ilmenite visible though very fine. 1% quartz-albite intergrowths. Nonmagnetic. No fizz. RQD 98%.											
		57264 2 cm gabbro vein 38 CA, beige halo, also 5 cm gray quartz vein with minor cubic pyrite. 57265 3 x 1 cm quartz veins with 3 cm peagreen halo with ilmenite altered to sphene. Sub- parallel to 57264. Grassgreen spots. No pyrite	57264	202.02 - 202.27	0.25			N 0.01	N 0	N 0.01		N	N 51 ppm W.
			57265	203.59 - 203.84	0.25			N 0.02	N 0	N 0		N	N 200 ppm Cr
207.35 - - 214.90	FINE GABBRO - SPHENE												
		Same gabbro but sphene instead ilmenite. FG sn RQD 90 - 85%.											
		57266 15 cm thick very fine gabbro dike ~45 CA with white 8 cm thick quartz vein parallel in center with peagreen halo. Barren. 51659 1 cm gray gy. 45 CA, minor pyrite <1/mm footballs. Minor fault gouge. 51660 green-beige halo, 1% pyrite.	57266	207.38 - 207.76	0.38			N 0.01	N 0	N 0		N	N 170 ppm Cr
			51659	214.25 - 214.40	0.15			N 0.01	N 0	F 0	N 0.01	N	
			51660	214.40 - 214.70	0.30					F 0.01			

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-13 Page 8 (END)

CLAIM POST RESOURCES INC., Kamiskotia Project

4-Corners Grid (L2000E is 35 az, Mag decl. 11 W)

Grid Location (m): L 1053 N - 1847 E

Map: G-3968 Township: ROBB TP. Claims: P 3011003- 19%
G-3986 JAMIESON P 3012747- 81%

UTM NAD 83 - Elevation 4 m below CP-10-13
17U 0455942 E - 5376465 N 7 m below CP-06-4

DDH Direction (azimuth) / Dip (plunge): 052/45 degrees

Hole Length: 317 m Core Diameter: NQ - 47 mm

Casing Length: 14 m Overburden Thickness: 9 m

Casing left in hole and capped, marked by wood post.

Other: Waterseam at 283.5 m, lost return to end.

Core stored in 72 trays at: 6076 King St., Porcupine, ON.

Water from CP-06-5, submersible, enough for a fire engine.

48 Samples (Continuous sawed half core):

51662-663, 57267-283, 57285-313.

Highlights:

From 29.00 m 0.29 m 0.04 g/t Au 0.20 % Zn

From 94.75 m 0.90 m 0.27 g/t Au 0.61 % Zn
ZnV2 to ZnV3 could be the same vein if about 232/63.

The adjacent fault here would cut above the vein,
and in CP-06-4 below it as that hole enters under it.
Sphalerite here is dull pale beige vs. sparkling mid-
brown in ZnV3, and darker brown in the other veins.

From 238.30 m 0.26 m 0.04 g/t Au

This is significant because the geology and also the
style of pyrite vein are the same as some 65m above
in CP-06-5 where it intersected 1.3 g/t Au over 4.87 m.

LOG of DDH CP-10-14

Page 1 of 11

Drilling Started: 1 FEB 2010 Finished: 8 FEB 2010

Drilled by Denis Crites Drilling Ltd., Porcupine.

Set-up checked by: Daxl Hole stopped by: Daxl

Logged by: H. Daxl, M.Sc.

Submitted and Signed:

<u>Dip-Acid Tests:</u>	0 m	45°	200 m 40°
	23 m	41°	302 m 39°
	101 m	41°	

Trace: 230 m horizontal, 196 m vertical.

Crosses: L1075 N - 1855 E.

L1150 N - 1881 E.

L1225 N - 1896 E.

Legend:

H Mohs' hardness, as measure of alteration.

M5 Magnetic like magnetite, M0 = nonmagnetic.

CA Degrees to core axis.

F5 Fizz like calcite as reaction to cold 10% HCl.

RQD % core length longer than 2.5 x diam, > 12cm.

Analyses

by Cattarello, Actlabs, or ALS. Pulverized most samples entirely.

Details on certificates and logs. A = Aqua regia - ICP,

F = 30 g Fire assay, N = 30 g Neutron activation,

T = 4-acid near Total - ICP W = Whole rock fusion.

CP - 10 - 14

#	Box	FROM -	#	Box	FROM -	#	Box	FROM -
1	13.00	(14m cans)	31	139.88		61	267.41	
2	17.07		32	144.08		62	271.69	
3	21.30		33	148.35		63	275.64	
4	25.50		34	152.57		64	279.97	
5	29.52		35	156.92		65	284.00	
6	33.83		36	161.10		66	288.34	
7	37.90		37	164.90		67	292.61	
8	42.19		38	169.16		68	296.90	
9	46.43		39	173.25		69	301.13	
10	50.59		40	177.55		70	305.43	
11	54.92		41	182.00		71	309.70	
12	59.23		42	186.14		72	313.87	
13	63.60		43	190.50			- 317.00	
14	67.87		44	194.80				FOH
15	72.08		45	199.02				
16	76.31		46	203.37				
17	80.55		47	207.63				
18	84.87		48	211.91				
19	89.13		49	216.18				
20	93.45		50	220.47				
21	97.50		51	224.67				
22	101.56		52	228.90				
23	105.77		53	233.14				
24	110.00		54	237.57				
25	114.32		55	241.88				
26	118.57		56	246.10				
27	122.77		57	250.48				
28	127.02		58	254.62				
29	131.24		59	259.00				
30	135.57		60	263.19				

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-14 Page 2

FROM - TO m	ROCK UNIT	S A M P L E			%	%	%	g/t	%	g/t	g/t	g/t	OTHERS - % - g/t
		NUMBER	FROM - TO m	LENGTH	Cu	Pb	Zn	Ag	S	Au	Au	Au	
0 - -13.00	OVERBURDEN (Casing to 14m) Clay at 10-25 cm per soil sampling.												
13.00 - -28.23	FINE GABBRO - ILMENITE - TONALITE DIKES FG il. Tdk. 13.00 - 16.20 Strongly weathered, stops 75 CA sharp. Plagioclase weathers brown. gray, fine-grained gabbro, 3-6% fine disseminated ilmenite H=4-5. Minor haloes of sphene after ilmenite near dike. 50% TONALITE as few dikes, diffuse pale gray, 15% mafics < 2mm interstitial, 50% plagiocla- se between 1 mm quartz grains visible where weathered to H=6, else H=7. Varily dark crackled. Probably dikes as per few gabbro xenoliths and quartz-albitic? fusion gashes < 1 cm. All nonmagnetic. Minor local fiss, strong above 17 m. RQD varies near 80%. Barren.												
	57267 Weathered tonalite, 5% q veins	57267	15.42 - 15.80	0.38	N	O	N	O	N	O	N	N	N 3.36% Na, N 5.5 ppm Th, N 2.6 ppm U
	57268 40% wallrock to tonalite. 5% qv with 8mm py.	57268	24.05 - 24.40	0.35	N 0.02	N	O	N	O	N 0.05	N	N	N 200 ppm Ni.
	57269 Tonalite, 15% qv.	57269	27.20 - 27.59	0.39	N	O	N	O	N	O	N	N	N 3.24% Na, N 4 ppm Th
28.23 - -33.00	FINE GABBRO - ILMENITE FG il. Medium-gray, fine-grained, gabbro, 5% ilmenite very homogeneous below 29.60 as quartz-veins stop, H=6. Nonmagnetic, no fiss, RQD 98%.	57270	29.00 - 29.29	0.29	N 0.20	N	O	N	O	N 0.04	N		

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-14 Page 3

FROM - TO m	ROCK UNIT	S A M P L E			%	%	%	g/t	%	g/t	g/t	g/t	OTHERS - %	- g/t
		NUMBER	FROM - TO m	LENGTH	Cu	Pb	Zn	Ag	S	Au	Au	Au		
33.00 - - 46.00	FINE MELAGABBRO - ILMENITE Transitions over 3m to melanocratic. FGilmel Dark gray. H = 5. Below 41 m very weakly magnetic with <1% magmatic interstitial pyrite. Moderate fizz throughout. Else as above.													
F40	34.58 Minas FAULT 40 CA. 57271 1% interstitial pyrite clusters. 3% ilmenite. Good for whole rock analysis.	57271	42.36 - 42.74	0.38	W 0	N 0.01	N 0	W 0.2	N 0.01	F 0	N	F 0	Pt	F 0 Pd.
46.00 - - 78.00	GREEN GABBRO - MAGNETITE mGG Medium-gray, medium-grained greenish plagioclase, locally melanocratic darker. H = 5-6. 1-2% epidote webbings or <1 cm veinlets seldom with quartz-chlorite. Local quartz-calcite veining 20-35 CA Weakly magnetic due to magnetite <1 mm but also ~3% inconspicuous 1 mm ilmenite. No fizz. RQD 98%. Local 1% magmatic pyrite. The green gabbro seems to be autoliths variably diffused in fine melagabbro.													
	57272 50% quartz-chlorite-calcite vein 30 CA 57273 20% q-calcite-chlorite-Kyan-epidote 20 CA 57274 18% quartz-calcite vein 20 CA 57275 5% epidote stringers, <1% interstitial py 1mm magnetite vein 77 CA,	57272	46.43 - 46.69	0.26		N 0.01	N 0		N 0		N			
		57273	53.30 - 53.60	0.30		N 0.02	N 0		N 0		N			
		57274	62.39 - 62.80	0.41		N 0.02	N 0		N 0		N			N 250 ppm Ni
		57275	69.50 - 69.95	0.45		N 0.01	N 0		N 0		N			

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-14 Page 4

FROM - TO m	ROCK UNIT	S A M P L E			%	%	%	g/t	%	g/t	g/t	OTHERS - % - g/t
		NUMBER	FROM - TO m	LENGTH	Cu	Pb	Zn	Ag	S	Au	Au	Au
78.00 - - 93.50	FINE MELAGABBRO											
	FG mel	Dark gray, 20% 1 mm white plagioclase, H=6-5 downhole, 2-1% quartz-calcite- chlorite veins downhole. The 3% ilmenite is inconspicuous due to dark colour.										
		Locally weakly magnetic. Moderate fizz due to plagioclase. RQD 98%. Barren. Rapid transitions.										
93.50 - - 105.90	FINE GABBRO - ILMENITE											
	FG il.mt	Medium-gray fine-grained ~3% fine ilmenite apparent but altered to pale-beige leucocore at 94.30 - 97.50 due to quartz-veins. H=4-5 downhole. 4% qv below 97.50.										
		Nonmagnetic, no fizz, RQD except for sub- parallel weathered joints, fault, and veins near 95%. Transitions. Else barren.										
F 35	94.40 - 94.75 FAULT 35 CA minor gouge, subpara llel to veining below. Some brown weathering. 96.25 - 97.50 Xenolith? Quartzarenite H=6, light olive-gray. Fizz where sharp weathering halo. No leucocore halo, which is due to quartz-veining subparallel to fault.	57276	94.40 - 94.75	0.35		N 0.07	N 0	N 0		N		
			94.75 - 95.65	0.90	GRADE:	0.61%	Zn	0.27	g/t Au / 0.90 m			Could be ZnV ₃ - ZnV ₂ if attitude ~232/63.
	57277 10% qv, 1% 1/mm pyrite cubes, trace sphalerite?	57277	94.75 - 95.18	0.43		N 0.13	N 0	N 0.38	F 0.26		N	
	57278 25% qv-calcite-beige sphalerite 30CA tr.py	57278	95.18 - 95.42	0.24		N 0.64	N 0	N 0.25	F 0.35		N	F Opt, F Optd.
	57279 similar to 57278, dull beige sphalerite.	57279	95.42 - 95.65	0.23		N 1.49	N 0	N 0.13	F 0.16		N	N 2.4 ppm Sg

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-14 Page 5

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-14 Page 6

FROM - TO m	ROCK UNIT	S A M P L E				%	%	%	g/t	%	g/t	g/t	OTHERS - % - g/t
		NUMBER	FROM - TO m	LENGTH	Cu	Pb	Zn	Ag	S	Au	Au	Au	
Apkdk	127.64 - 128.10 APLITE DIKE, pink-gray, straight coin-granular fractures, diffuse. H = 7. Contacts 27 and 17 CA subparallel. Weakly magnetic. No fizz.												
	57286 50.10 3 cm gray calcite vein 7 CA. Some patches of magnetite.	57286	128.93 - 129.33	0.40	N	N	N	O	N	O	F	O	N N 13% Ca. F O Pt, F O Pd.
134.00 - - 149.25	FINE GABBRO - ILMENITE												
FG il	Medium-gray, 1-3% fine ilmenite some below 142 m is often altered to leucocrite. 3% quartz-albite veins < 5 cm thick. H=5-6. Nonmagnetic, no fizz, RQD 98%. Else barren.												
	57287 6 cm white QV 70 CA. Minor pyrite halo.	57287	140.30 - 140.71	0.41	N	0.02	N	O	N	O	N		
149.25 - - 161.85	META-SANDSTONE XENOLITHS												
xenoS	Pale-olive to medium-gray mottled as dark minerals become sericitized. Local diffuse quartz granules. No bedding. H=7. Two xenoliths separated by fine ilmenite gabbro at 153.80 - 156.40. Nonmagnetic, No fizz. RQD 95% to 160.70. Then 50% due to faults. Lower contact 65 CA.												
	149.25 - 149.90 60% quartz-calcite-albite veining, barren, subparallel to core axis to 10 CA. Else 3% similar veins < 5 cm thick. 57288.	57288	149.53 - 149.98	0.45	N	0.01	N	O	N	0.03	F	O	N N 11% Ca. F O Pt, F O Pd.

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-14 Page 7

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-14 Page 8

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-14 Page 9

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-14 Page 10

FROM - - TO m	ROCK UNIT	SAMPLE			% Cu	% Pb	% Zn	% Ag	% S	g/t Au	g/t Au	g/t Au	OTHERS - % - g/t
		NUMBER	FROM - TO m	LENGTH									
	Light olive gray, locally diffuse dark gray, variably fractured with pale or dark halos. Apparently after a sandstone though no bedding, molten by the gabbro intrusion. Quartz grains < 5 mm in 1 mm diffuse grain with interstitial sericitic? H=7.												
	Few quartz veins to 247m and below 267m. Nonmagnetic. No fiss., RQD 98%, barren. Lower contact 52 CA with parallel magmatic alignment to 273m and ilmenite persisting.												
57299	10% q-chlorite-plag ² vein, 3% gabbro injections.	57299	246.29 - 246.79	0.50	N	N	O	N	O	F	O	N	ppm: 2.3 U, 5.8 Th, 56 La, 134 Ce, 65 Nd, 17 Sm, 4 Eu, 3 Tb, 19 Yb, 3 Lu.
57300	15% quartz-calcite veins.	57300	246.79 - 247.24	0.45	N	N	O	N	O			N	Lanthanides,
57301	1cm qc. 40% gabbro injections	57301	249.96 - 250.40	0.46	N	N	O	N	O	N	ppm: 8 Th, 2 U, 49 La, 105 Ce, 50 Nd,		
57302	10% gabbro injections.	57302	252.65 - 253.07	0.42	N	N	O	N	O	N	ppm: 1120 ppm Ni, N 2.95%, Na, Lanthanides,		
57303	trace pyrrhotite-chlorite stringer 24 CA.	57303	257.29 - 257.71	0.42	N	N	O	N	0.01	N	ppm: 16 Hf, 8 Th, 3 U, 50 La, 15 Ce, 4 Nd.		
57304	20% quartz-chlorite-plag. vein stringer 1 cm	57304	259.26 - 259.74	0.48	N	N	O	N	O	F	O	N	ppm: 7 Th, 4 La, 99 Ce, 45 Nd, 12 Sm, F O, Pt, F O, Pd.
57305	rare pyrrhotite. Trace round 1 mm quartz grains	57305	266.11 - 266.48	0.37	N	0.01	N	O	N	N	ppm: 7 Th, 3 U, 50 La, 125 Ce, 53 Nd, 14 Sm, 20 Yb.		
57306	1% < 2 mm pyrrhotite cubes along fractures	57306	268.60 - 269.00	0.40	N	N	O	N	O	N	ppm: 16 Hf, 7 Th, 18 La, 110 Ce, 45 Nd, 13 Sm, 21 Yb.		
57307	ditto.	57307	269.00 - 269.45	0.45	N	N	O	N	0.01	N	ppm: 7 Th, 50 La, 120 Ce, 59 Nd, 14 Sm, 20 Yb.		
57308	1 cm quartz-vein perpendicular to contact.	57308	271.69 - 272.00	0.31	N	N	O	N	O	N	ppm: 7 Th, 3 U, 44 La, 99 Ce, 52 Nd, 13 Sm.		
272.00 - - 317 EOH	FINE MELAGABBRO - PYROXENITE - ILMENITE												
PFG il	Dark gray. Very fine interstitial near 10% plagioclase, now pieces like calcite. Det pyroxene are dark green. Possibly a pyroxenite with calcite? H=5. Quite homogeneous with 1% calcite veinlets < 1 cm without locally minor quartz. To 273 m pale fine diffuse plagioclase infiltration.												NOTE: TONALITE HAS NOTICEABLY MORE Th, U, Hf, Na and Lanthanides, BUT LESS Sc, Fe, AND NO GOLD! See analyses for more.

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-14 Page 11 (END)

CLAIM POST RESOURCES INC., Kamiskotia Project

4-Corners Grid (L2000E is 35 az, Mag decl. 11 W)

Grid Location (m): L 1060 N - 1750 E

Map: G-3968 Township: ROBB JAMIESON Claims: P3011003 - 60%
G-3986 GODFREY P3012747 - 29%
UTM NAD 83 - Elevation 3 m below CP-10-13 P3010919 - 11%

17U 0455868 E - 5376528 N

DDH Direction (azimuth) / Dip (plunge): 147/45 degrees

Hole Length: 466 m Core Diameter: NQ - 47 mm

Casing Length: 15 m Overburden Thickness: 9 m

Casing left in hole and capped, marked by wood post.

Other: Lost water return at 183 m to end.

Core stored in 107 trays at: 6076 King St., Porcupine, ON.

Water from CP-06-5, submersible, enough for a fire engine.

68 Samples (Continuous sawed half core):

51664-669, 57315-331, 57333-355, 57357-373,
57375-379.

Highlights:

From m	g/t Au	g/t Ag	% Zn
--------	--------	--------	------

243.12	0.24m	0.06	1.90	1.05	4cm q - sl vein 72CA.
245.23	0.27m	0.10	5.00	1.88	10cm q - sl vein 50CA.
296.54	0.41m	0.04	1.00	0.44	10% q - veins 53 CA with sl cusps.
342.12	0.26m	0.32	2.30	6.35	9cm sl - q - cc vein 68CA.
365.31	0.25m	0	0	0.74	2% sl veinlets 85CA.
434.00	0.26m	0.04	2.45	3.71	Cc -q 65CA, 7cm sl center.

LOG of DDH CP-10-15

Page 1 of 14

Drilling Started: 8 FEB 2010 Finished: 14 FEB 2010

Drilled by Denis Crites Drilling Ltd., Porcupine.

Set-up checked by: Daxl Hole stopped by: Daxl

Logged by: H. Daxl, M.Sc.

Submitted and Signed: 

<u>Dip-Acid Tests:</u>	0 m	45°	242 m	38°
	32 m	41°	266 m	39°
	101 m	40°	302 m	39°
	203 m	39°	404 m	40°

Trace: 358 m horizontal, 297 m vertical.

Crosses: L1000N - 1889E.

L 925N - 2075E.

L 2000E - 955N.

Legend:

H Mohs' hardness, as measure of alteration.

M5 Magnetic like magnetite, M0 = nonmagnetic.

CA Degrees to core axis.

F5 Fizz like calcite as reaction to cold 10% HCl.

RQD % core length longer than 2.5 x diam, >12cm.

Analyses

by Cattarello, Actlabs, or ALS. Pulverized most samples entirely.

Details on certificates and logs. A = Aqua regia - ICP,

F = 30 g Fire assay, N = 30 g Neutron activation,

T = 4-acid near Total - ICP

W = Whole rock fusion.

CP-10-15

BOX #	FROM - m	BOX #	FROM - m	BOX #	FROM - m	BOX #	FROM - (m)
1	13.00 (casing to 15m)	31	137.38	62	270.00	95	412.72
2	16.50	32	141.70	63	274.32	96	417.01
3	19.79	33	145.90	64	278.54	97	421.42
4	23.96	34	150.10	65	282.93	98	425.65
5	28.38	35	154.40	66	287.27	99	430.02
6	32.65	36	158.58	67	291.58	100	434.35
7	36.88	37	163.01	68	295.80	101	438.69
8	41.00	38	167.22	69	300.20	102	443.00
9	45.13	39	171.50	70	304.48	103	447.42
10	49.08	40	175.89	71	308.81	104	451.78
11	53.18	41	180.18	72	313.27	105	456.17
12	57.46	42	184.53	73	317.50	106	460.44
13	61.64	43	188.69	74	321.78	107	464.73
14	65.79	44	193.09	75	326.11		- 466.22
15	69.90	45	197.40	76	330.50		EDH
16	74.00	46	201.73	77	334.80		
17	78.28	47	206.00	78	339.08		
18	82.49	48	210.20	79	343.48		
19	86.76	49	214.48	80	347.74		
20	91.02	50	218.74	81	352.15		
21	95.18	51	222.91	82	356.44		
22	99.40	52	227.22	83	360.79		
23	103.58	53	231.47	84	365.06		
24	107.86	54	235.77	85	369.44		
25	112.10	55	239.98	86	373.83		
26	116.30	56	244.30	87	378.18		
27	120.50	57	248.55	88	382.57		
28	124.76	58	252.90	89	386.98		
29	128.91	59	257.21	90	391.22		
30	133.13	60	261.45	91	395.38		
		61	265.68	92	399.67		
				93	404.00		
				94	408.38		

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-15 Page 2

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-15 Page 3

FROM - - TO m	ROCK UNIT	S A M P L E			%	%	%	g/t	%	g/t	g/t	OTHERS - % - g/t
		NUMBER	FROM - TO m	LENGTH	Cu	Pb	Zn	Ag	S	Au	Au	Au
		57317	10% quartz-calcite-dolomite veinings 10 CA.	57317 29.34 - 29.81	0.47				N 0.01	N 0	N 0	N
32.00 - - 36.00	GABBRO - ILMENITE - MAGNETIC											
m Gil	Gradational zone of mesogabbro with medium grained slightly greenish plagioclase. H=5-6.											
	Massive Barren. Normal ilmenite.											
	Moderately magnetic in center grading away to margins. No fizz. RQD 98%.											
	57318 6% ilmenite <1mm, for whole rock anal.	57318	32.64 - 32.90	0.26	W 0	W 0	N 0.02	N 0	N 0	F 0	N	F 0 Pt, F 0 Pd.
36.00 - - 37.70	FINE MELA GABBRO - ILMENITE				W 0	W 0	W 0.02	W 0	W 0.1			W + 57318 IRON ORE FUSION-XRF
	Continued.											% 45.80 SiO ₂ 11.72 Fe
FG Gil mel	Sphene gradually appears.											13.90 Al ₂ O ₃ , 4.04 MgO
37.70 - - 47.60	FINE GABBRO - SPHENE											7.35 CaO, 3.49 TiO ₂
FG Sph mel	Medium-gray mesocratic 5-8% sphene. H=3-4 due to minor shear near 90 CA. Nonmagnetic. Variable fizz. RQD 50 CA.											3.22 Na ₂ O 0.18 Mn
	shear 90 Several 1 cm quartz-veins near 90 CA to 42 m coincide with shear. Minerals are somewhat aligned except sphene which suggests magmatic alignment as Ti-minerals are first to crystallize. This facilitated the minor shear. 1 cm fault gouge only at 39.75 ~ 90 CA											0.13 K ₂ O 0.09 P
	Brown weathering of veins and much gabbro below 45.30 as plagioclase weathers brown.											ppm 300 V, 45 Cr, 0 Cr, 11 Ni, 199 Sr W + ppm Nb

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-15 Page 4

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-15 Page 5

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-15 Page 6

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-15 Page 7

FROM - TO m	ROCK UNIT	S A M P L E			%	%	%	g/t	g/t	g/t	OTHERS - % - g/t	
		NUMBER	FROM - TO m	LENGTH	Cu	Pb	Zn	Ag	S	Au	Au	
57335	1% pyrr. cubes < 2 mm	57335	140.00 - 140.16	0.16			N O	N O		N O	F O	N F O Pt, F O Pd
150.84 - 151.30	30% quartz-calcite breccia matrix, Trace 1 mm pyrr. cubes.	57336	150.82 - 151.06	0.24			N O	N O		N O		N
151.06 - 151.27		57337	151.06 - 151.27	0.21			N O	N O		N O		N
152.00	1 cm sud vein along core.											
153.85 - 154.25	Barren sud 2 cm vein 12 CA.	57338	153.87 - 154.18	0.31			N O	N O		N D	F 0.01	N
156.90 - 157.10	2 cm sud vein with one 1 cm py. cube	57339	157.00 - 157.27	0.27			N O	N O		N O		N N 1 ppm As
157.35	6 cm barren sud vein 50 CA.											
157.90 - 158.56	50% quartz-calcite-chlorite - trace py <1 cm cubes, probably same breccia vein along hole as below.	57340	158.26 - 158.59	0.33			N O	N O		N O	F O	N F O Pt, F O Pd
159.30 - 161.00	Quartz-calcite-chlorite vein along hole, barren. Ilmenite not affected, no halo. 4 cm thick.	57341	159.60 - 159.83	0.23			N O	N O		N O		N N 10% Ca
		57342	160.06 - 160.28	0.22			N O	N O		N O		N
		57343	160.60 - 160.89	0.29			N O	N O		N O		N N 2.1% Na
Vg 0	151 - 161 m as described above.											
Bdk	168.55 - 169.83 BASALT DIKE contacts 62 and 75 CA with <3 cm halo of sphene after ilmenite. H = 6.											
173.51 - 173.53	2 cm quartz-calcite-magnetite-pyrite vein 75 CA with 10 cm sharp chloritized halo with Sphene after ilmenite of gabbro downhole only.											
Vg	178.53 - 178.74 Pure white quartz-vein 30-40 CA. one py. cluster. 1 cm pure albite vein 15 CA oblique to it Branches from it uphole. Gradual silicification halo uphole to 177 m and to 185 from vein below, but ilmenite not affected except for few grains sphene.	57344	178.40 - 178.58	0.18			N O	N O		N O		N

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-15 Page 8

FROM - TO m	ROCK UNIT	S A M P L E			% Cu	% Pb	% Zn	% Ag	% S	g/t Au	g/t Au	g/t Au	OTHERS - % - g/t
		NUMBER	FROM - TO m	LENGTH									
F 50	182.90 - 183.10 FAULT 50 CA, 10 cm abrupt weathering halos from 2 cm quartz vein at down-hole margin of 65 cm LEUCOGABBRO dike, H=4-5, all sub parallel. 50 cm leucosome halo down-hole.	57345	182.93 - 183.13	0.20				N	N	0	N 0.08		N ppm 16 As, 27 W, 30 La, 82 Ga, 38 Nd
W	183.00 m WATER SEAM - Lost water return to end												
Vg 20	183.80 - 184.25 White Quartz-vein 20 CA, barren, albite selvage, 10 cm thick branch up-dip.	57346	183.70 - 184.00	0.30				N	N	0	N 0		N
	57347 Very fine pyrite plating 23 CA fracture, also 1 cm quartz-calcite vein 50 CA perpendicular to it. Sphene halo 40 cm.	57347	190.75 - 191.00	0.25				N 0.02	N	0	N 0		N
191.00 - -235.50	GREEN GABBRO - ILMENITE												
GGil	Medium- to dark greenish gray. 30-40% 2mm greenish-white plagioclase often as lathes in dark-greenish matrix mass. Seldom melanocratic or pyroxenite. Quite homogeneous. H=6. 3-5% fine rectangular to cuspatate ilmenite not conspicuous. Trace pyrite. Locally weakly magnetic. No fizz. ROD 95%. Barren.												
Bdk 40	192.70 - 193.47 BASALT DIKE medium-gray, olivinic margins 35-45 CA. H=5-6. Nonmagnetic. Moderate to strong fizz. Barren. Wall rock not affected nor ilmenite.												
	57348 1cm quartz-epidote vein 30 CA. Few py as halo?	57348	198.47 - 198.70	0.23				N 0.02	N	0	N 0		N
	57349 8% quartz-epidote veins in deuteric zone.	57349	223.36 - 223.62	0.26				N 0.03	N	0	N 0		N

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-15 Page 9

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-15 Page 10

FROM - TO m	ROCK UNIT	S A M P L E			%	%	%	g/t	%	g/t	g/t	g/t	OTHERS - % - g/t
		NUMBER	FROM - TO m	LENGTH	Cu	Pb	Zn	Ag	S	Au	Au	Au	
	2-5% fine to very fine ilmenite throughout.												
	Locally weakly magnetic. Local minor fiss. RQD 98-90 downhole. Else barren.												
	57355 35% quartz-calcite-black tourmaline? - magnetite veins 55 CA with <5mm pyrite cubes.	57355	275.40 - 275.60	0.20					N 0.05	N 0	N 0	F 0	N N 13.5% Fe, F 0 Pt, F 0 Pd
286.70 -	GABBRO DIKE - 50 CA												
-292.52	Up-hole contact 55 CA with chilled margin, Gdk 50 no halo. Lower contact similar but less certain. Center fine-grained anhedral plagioclase often beige to pinkish hue. Black grains may be just magnetite, H=6. Calcite vein with pink K-cpx? halo at 289.75.												
	291.10 MINOR FAULT 50 CA with minor weathered plating.												
	Weakly magnetic. No fiss. RQD 80%. Barren.												
292.52 -	FINE MELAGABBRO - ILMENITE	57356	STAND. OREASH 3	✓									
-308.00	3-5% ilmenite. H=5-6. 3% <3cm quartz-calcite veins. Seldom weakly magnetic. Moderate fiss of plagioclase. RQD 98%. Barren.												
F60	307.00 MINOR FAULT 60 CA along quartz-calcite <cm vein with <5cm leucoxene halo. No halo at others.								A 0.43 A 1				Appm: 40 As, 44 Cd.
V06L 53	51667 10% qv 53 CA, 1% honey-beige sphalerite as <5mm patches and cusps in quartz. No halo.	51667	296.54 - 296.95	0.41	A 0	A 0	N 0.44	N 0	A 0.4	F 0.04	N 0.03	F 0.06	N. F 0 Pt, 0 Pd.

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-15 Page 1

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-15 Page 12

FROM - TO m	ROCK UNIT	S A M P L E			% Cu	% Pb	% Zn	% Ag	% S	g/t Au	g/t Au	g/t Au	OTHERS - % - g/t
		NUMBER	FROM - TO m	LENGTH									
		51668	342.12 - 342.38	0.26	T 0.01	T 0	T 5.95	T 2.6	T 3.6	F 0.35	F 0.31	N 0.30	N T
	9 cm thick sphalerite-quartz-calcite vein 68 CA with few <5 mm pyrite cubes. Chloritic halo but ilmenite not affected. Sphalerite is beige- yellow, too fine to glitter. Nonconductive always.	51668	342.12 - 342.38	0.26	A 0.01	A 0	A 6.74	A 2	A 4.2			F 0.30	F O Pt, F O Pd, T 778 ppm Cd F O Rh. Appm 691 Cd, 73 Co, 20 As, 50 W, 6 V
344.00 -	GREEN GABBRO-ILMENITE												
-398.00	30-40% 2 mm greenish-white plagioclase GG il laths in dark greenish mafic mass. H=6. Mostly quite homogeneous but fine zones at 363-368 where chloritic at 365-366.30 H=4. Also fine around other veins but not chloritic. 3-5% fine ilmenite is inconspicuous. Fine zones have <10% quartz-calcite veins <2 cm. Only <0.3% epidote veinlets. No haloes. 346.50 Aplitic dikelets 2 and 4 cm. The fine zones may be deuterian pyroxenite? 357.50 Hornfels plotting 25CA. 368-372 Weakly magnetic else locally very weakly. No fizz. RQD 98%. Else barren.												
57361	Minor quartz flooding.	57361	364.52 - 364.79	0.27					N 0.02	N 0	N 0	N	N 2.24% Na
57362	10% quartz-calcite veins, local chloritic.	57362	364.79 - 365.06	0.27					N 0	N 0	N 0	N	
57363	30% qc-veins with few <2 mm py cube H=4	57363	365.06 - 365.31	0.25					N 0.03	N 0	N 0	N	
57364	2% il veinlets 85 CA parallel to minor shear. Chloritic and talcose H=3-4. 10% qc veining.	57364	365.31 - 365.56	0.25	A 0	A 0	N 0.76	A 8	A 0.9	N 0	F 0	N A	N 15 ppm As, F O Pt, F O Pd, A 144 ppm Cd
57365	H=3-4. 3% quartz-calcite veinlets. il same.	57365	365.56 - 365.80	0.24					N 0.03	N 0	N 0	N	N 17 ppm As
57366	8% quartz-pinkish calcite veining, tr. py.	57366	372.40 - 372.72	0.32					N 0.02	N 0	N 0	N	
57367	10% quartz-calcite-epidote vein 50 CA.	57367	383.68 - 383.93	0.25					N 0.01	N 0	N 0	N	N 2.3% Na
57368	6 cm quartz-calcite-chlorite vein 90 CA.	57368	389.24 - 389.49	0.25					N 0.02	N 0	N 0	N	

CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-15 Page 13


CLAIM POST RESOURCES INC., Kamiskotia Project, LOG of DDH CP-10-15 Page 14 (END)

FROM - TO m	ROCK UNIT	S A M P L E			%	%	%	%	g/t	g/t	g/t	OTHERS - % - g/t
		NUMBER	FROM - TO m	LENGTH	Cu	Pb	Zn	Ag	S	Au	Au	
	Locally weakly magnetic. No fizz. RQD 98%.											
	Barren.											
448.00 - -451.95	FINE MELAGABBRO - ILMENITE											
	5% quartz-calcite veins. H=6. Nonmagnetic.											
FG melil	Variable fizz. RQD 95%. Barren. 3% ilmenite.											
.ACV												
	51375 6% quartz-calcite-chlorite veining with few ankerite? brownish triangular euhedra.	57375	449.84 - 450.25	0.41				N 0.02	N 0	N 0	N	N 40 ppm As, N 2.28% Na
	51376 Acron contact includes 5 cm chalcopyrite below.	57376	451.78 - 452.00	0.22				N 0.02	N 0	N 0	N	
	All H=4. 10% calcite veining.											
451.95 - -466. FOH	GRAY GABBRO - YOUNGER - ILMENITE											
younger gray G. il	Whole contact chilled chloritic H=4 at 48 CA. Aphanitic margin to fine-grained H=6 by 456 m. Dark blackish gray. Mesocratic as plagioclase is gray. Stays fine-grained or very fine-grained but below 464 m plagioclase forms diffuse elongate groupings. 50 CA as gabbro turns melanocratic H=5 and 1 mm diffuse ilmenite becomes < 8%.										*	57379 IRON ORE FUSION-XRF
	456.20 - 464.00 5% quartz-calcite veining < 5 cm. Below 465.40 m weakly magnetic. Strong fizz of plagioclase throughout. RQD 95%. Else barren.										%	45.80 SiO ₂ 11.68 Fe
												11.10 Al ₂ O ₃ , 4.28 MgO
												7.13 CaO, 2.56 TiO ₂
												2.29 Na ₂ O 0.17 Mn
												2.59 K ₂ O 0.19 P
												ppm: 358 V, 43 Cr, 60 Gr, 48 Ni.
												W ppm: 9 Nb, 109 Rb, 224 Zr.
466.22	END OF HOLE	57377	456.26 - 456.58	0.32				N 0.13	N 0	N 0	N	N 52 ppm As
	51378 50% silicified and 1 cm sphalerite in sample.	57378	456.58 - 456.88	0.30				N 0.10	N 0	N 0	N	N 37 ppm As
	51379 For whole-rock analysis. 5% diffuse ilmenite	57379	465.15 - 465.38	0.23				W 0	W 0	N 0	NW*	Fo At, Fo Pd,
								W 0	W 0	W 0		

Scale: 1:5000




NAD 83 - 5377000N



Location of CP-10-12 to 15

Claim Post Resources Inc.

4-Corners Area, Kamiskotia Project
Diamond Drilling of Jan - Feb 2010
Hermann Daxl, M.Sc. 31 Dec 2010



CP-10-12

133.50 - 137.06 3.56 Massive Magnetite Dike,
moderate conductor, 63.4% Fe, 0.84% TiO₂, 771 ppm V,
no Cr Ni Co Nb S.


From	To	m	%Cu	g/t Au	g/t Ag	
111.46	111.88	0.42	0.37	0.25	5.40	photos
112.19	112.48	0.29	0.01	2.00	3.00	photos
173.40	174.49	1.09		0.27		
184.76	185.49	0.73		0.37		
140.00	217.00	77.00				further traces of gold in gabbro as quartz-veins are frequent and various pyrite bears gold.
206.22	206.49	0.27	0.45	0.14	2.90	

Rock Units:

- B Basalt
- FG Fine- to very fine-grained gabbro, usually dark gray with black specks well visible on dry core. These are ilmenite (il), subhedral, 0.5 to 2mm, < 15% disseminated, or magnetite-ilmenite intergrowth when magnetic (mil).
- mFGil When altered to sphene (sn) near quartz-veins the gabbro is somewhat brownish. When altered to leucoxene (lx) the pale-buff grains of same habit are visible on wet core.
- GG Green medium-grained gabbro, plagioclase is greenish due to epidote which also occurs as anastomosing veinlets locally.
- mGG Usually magnetic (m), with ilmenite but not so apparent, transitional from mFGit.
- G Medium-grained gray gabbro, usually melanocratic with white plagioclase laths, nonmagnetic, sparse ilmenite but not apparent. Possibly an older intrusion.
- P, GP Pyroxenite, G with local pyroxenite.
- S Sandstone, well sorted, rounded, and packed <2mm clean cemented pale beige quartz. No bedding.
- T Tonalite, diffusely medium-grained, variably 10% dark mafics, probably metamorphosed sandstone.

DDH CP-10-12
Section L 1300 N

Claim Post Resources Inc.
4-Corners Area, Kamiskotia Project
Diamond Drilling of Jan - Feb 2010
Hermann Daxl, M.Sc. 31 Dec 2010



CP-10-13

Gold zone 285/70 at 455931E-5376623N as per outcrop and soils (T-5809), was not intersected although nearby. Outcrop - Au: #3012 - 344ppb, 3021 - 288, 3022 - 352.

ZnV3 was not intersected and therefore is unlikely to run sub-vertical with its acute angle to CP-06-4 (T-5615).

The strong deep IP anomaly (T-5428) at L1150N-1775E was not intersected unless due to ubiquitous laminated ilmenite-hematite, which would act like a capacitor.

Legend and Rock Description:

Rock Units:

B	Basalt
FG	Fine- to very fine-grained gabbro, usually dark gray with black specks well visible on dry core. These are ilmenite (il), subhedral, 0.5 to 2mm, <15% disseminated, or
mFGil	magnetite-ilmenite intergrowth when magnetic (mil).
FGsn	When altered to sphene (sn) near quartz-veins the gabbro
FGlx	is somewhat brownish. When altered to leucoxene (lx) the pale-buff grains of same habit are visible on wet core.
GG	Green medium-grained gabbro, plagioclase is greenish due to epidote which also occurs as anastomosing veinlets locally.
mGG	Usually magnetic (m), with ilmenite but not so apparent, transitional from mFGil.
G	Medium-grained gray gabbro, usually melanocratic with white plagioclase laths, nonmagnetic, sparse ilmenite but not apparent. Possibly an older intrusion.
P, GP	Pyroxenite, G with local pyroxenite.
S	Sandstone, well sorted, rounded, and packed <2mm clean cemented pale beige quartz. No bedding.
T	Tonalite, diffusely medium-grained, variably 10% dark mafics, probably metamorphosed sandstone.

Structure:

F30	Fault at 30 degrees to core axis (CA), evidenced by shear, broken core, or some gouge. FZ is wider fault zone.
FZ	
Vqc	Veins of quartz-calcite. QV >15cm thick.
W	Water seam, as reported by drillers, or at limonite alteration.

Minerals:


cp	chalcopyrite	m	magnetic
py	pyrite	il	ilmenite
sl	sphalerite	sn	sphene
mt	magnetite	lx	leucoxene

Main values plotted:

Au Ag in g/t, Cu Zn in %, over m: 0.32Au, 2.30Ag, 6.35Zn/0.24

DDH **CP-10-13**

Claim Post Resources Inc.
4-Corners Area, Kamiskotia Project
Diamond Drilling of Jan - Feb 2010
Hermann Dox, M.Sc. 31 Dec 2010



CP-10-14

From 29.00 m 0.29 m 0.04 g/t Au 0.20 % Zr

From 94.75 m 0.90 m 0.27 g/t Au 0.61 % Zn
ZnV2 to ZnV3 could be the same vein if about 232/63
The adjacent fault here would cut above the vein,
and in CP-06-4 below it as that hole enters under it.
Sphalerite here is dull pale beige vs. sparkling mid-
brown in ZnV3, and darker brown in the other veins.

From 238.30 m 0.26 m 0.04 g/t Au
This is significant because the geology and also the style of pyrite vein are the same as some 65m above in CP-06-5 where it intersected 1.3 g/t Au over 4.87 m

Legend and Rock Description:

Rock Units

B	Basalt
FG	Fine- to very fine-grained gabbro, usually dark gray with black specks well visible on dry core. These are ilmenite (il), subhedral, 0.5 to 2mm, <15% disseminated, or
FGil	magnetite-ilmenite intergrowth when magnetic (mil).
FGsn	When altered to sphene (sn) near quartz-veins the gabbro is somewhat brownish. When altered to leucoxene (lx)
FGlx	the pale-buff grains of same habit are visible on wet core.
GG	Green medium-grained gabbro, plagioclase is greenish due to epidote which also occurs as anastomosing veinlets locally.
mGG	Usually magnetic (m), with ilmenite but not so apparent, transitional from mFGil.
G	Medium-grained gray gabbro, usually melanocratic with white plagioclase laths, nonmagnetic, sparse ilmenite but not apparent. Possibly an older intrusion.
P, GP	Pyroxenite, G with local pyroxenite.
S	Sandstone, well sorted, rounded, and packed <2mm clean cemented pale beige quartz. No bedding.
T	Tonalite, diffusely medium-grained, variably 10% dark mafics, probably metamorphosed sandstone.

Structure

F30	Fault at 30 degrees to core axis (CA), evidenced by shear, broken core, or some gauge. FZ is wider fault zone.
Vqc	Veins of quartz-calcite. QV > 15cm thick.
W	Water seam, as reported by drillers, or at limonite alteration.

Minerals

cp	chalcopyrite	m	magnetic
py	pyrite	il	ilmenite
sl	sphalerite	sn	sphene
mt	magnetite	lx	leucoxene

Main values plotted


Au Ag in g/t, Cu Zn in %, over m: 0.32Au.2.30Ag.6.35Zn/0.26


Collar at UTM
NAD83 17U
455942 E - 5376465 N
4m below CP-10-13


Scale 1 : 1500


DDH CP-10 -14


Claim Post Resources Inc.
4-Corners Area, Kamiskotia Project
Diamond Drilling of Jan - Feb 2010
Hermann Daxl, M.Sc. 31 Dec 2010














Neutron Activation "1 Denh"

Activation Laboratories Ltd.

Report: A10-8902

Analyte Symbol	Au	Ag	As	Ba	Br	Ca	Co	Cr	Cs	Fe	Hf	Hg	Ir	Mo	Na	Ni	Rb	Sb	Sc	Se
Unit Symbol	ppb	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	%	ppm	ppm	ppm	ppm	
Detection Limit	2	5	0.5	50	0.5	1	1	5	1	0.01	1	1	5	1	0.01	20	15	0.1	3	
Analysis Method	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	
679	38	< 5	4.1	310	10.4	< 1	6	56	< 1	1.00	2	< 1	< 5	< 1	0.70	< 20	52	0.9	4.1	< 3
680	4	< 5	1.8	440	6.1	2	5	75	< 1	1.27	8	< 1	< 5	< 1	1.99	< 20	47	0.2	5.5	< 3
681	< 2	< 5	4.1	< 50	14.6	< 1	5	7	< 1	0.22	< 1	< 1	< 5	< 1	0.06	< 20	< 15	0.5	0.5	< 3
682	6	< 5	4.5	< 50	10.3	< 1	3	14	< 1	0.31	< 1	< 1	< 5	< 1	0.08	< 20	23	0.9	1.1	< 3
683	23	< 5	1.7	< 50	10.3	< 1	4	6	< 1	0.19	< 1	< 1	< 5	< 1	0.05	< 20	< 15	0.4	0.5	< 3
684	< 2	< 5	2.0	90	8.5	< 1	4	15	< 1	0.21	< 1	< 1	< 5	< 1	0.06	< 20	< 15	0.4	0.7	< 3
685	< 2	< 5	1.3	< 50	10.1	2	3	9	< 1	0.22	< 1	< 1	< 5	< 1	0.08	< 20	< 15	0.4	0.6	< 3
686 SAND at 687	< 2	< 5	1.6	440	7.0	< 1	11	54	< 1	1.94	7	< 1	< 5	< 1	1.81	< 20	69	< 0.1	6.6	< 3
687	10	< 5	2.3	140	11.0	< 1	5	11	< 1	0.38	2	< 1	< 5	< 1	0.31	< 20	< 15	0.5	1.2	< 3
688	7	< 5	3.2	< 50	15.8	4	5	9	< 1	0.25	< 1	< 1	< 5	< 1	0.05	< 20	< 15	0.4	0.7	< 3
689 Hwy showing 1960	< 5	2.6	360	4.9	2	6	40	< 1	1.35	5	< 1	< 5	< 1	1.47	< 20	< 15	0.2	5.9	< 3	
690 near -" -	7	< 5	3.1	130	11.5	< 1	6	7	< 1	0.43	< 1	< 1	< 5	< 1	0.22	< 20	< 15	0.7	1.4	< 3
691	22	< 5	3.0	120	16.4	2	3	10	< 1	0.28	< 1	< 1	< 5	< 1	0.07	< 20	< 15	0.7	0.8	< 3
692	9	< 5	1.7	130	13.4	2	3	6	< 1	0.19	< 1	< 1	< 5	< 1	0.04	< 20	< 15	0.4	0.7	< 3
693	13	< 5	4.1	< 50	17.9	< 1	10	10	< 1	0.35	< 1	< 1	< 5	< 1	0.07	< 20	< 15	0.8	1.1	< 3
694	< 2	< 5	2.6	70	13.1	3	5	< 5	< 1	0.35	< 1	< 1	< 5	< 1	0.07	< 20	< 15	0.6	1.0	< 3
695	9	< 5	2.3	< 50	12.4	2	4	< 5	< 1	0.21	< 1	< 1	< 5	< 1	0.05	< 20	< 15	0.5	0.7	< 3
696	< 2	< 5	2.0	< 50	10.4	3	2	6	< 1	0.15	< 1	< 1	< 5	< 1	0.04	< 20	< 15	0.4	0.4	< 3
697	4	< 5	3.1	< 50	11.2	2	4	9	< 1	0.25	< 1	< 1	< 5	< 1	0.07	< 20	< 15	0.6	0.9	< 3
698	< 2	< 5	2.4	100	11.4	< 1	4	7	< 1	0.21	< 1	< 1	< 5	< 1	0.06	< 20	39	0.4	0.7	< 3
699	< 2	< 5	3.9	< 50	19.8	2	6	10	< 1	0.27	< 1	< 1	< 5	< 1	0.07	< 20	< 15	0.6	0.7	< 3
700 AREAS 42P 111 vs. 91	< 5	111.0 ✓	560 ✓	3.8	< 1 ✓	63	1340	8	8.81 ✓	5	< 1	< 5	7 ✓	0.13 ✓	690 vs. 42P	155	14.3	16.1	< 3	
782	< 2	< 5	2.5	410	6.9	< 1	8	85	< 1	2.38	8	< 1	< 5	< 1	1.91	< 20	37	< 0.1	6.7	< 3
783	< 2	< 5	2.4	250	9.7	2	5	36	< 1	0.65	4	< 1	< 5	< 1	0.92	< 20	53	0.4	2.6	< 3
784	< 2	< 5	1.5	310	3.9	< 1	3	25	< 1	0.74	3	< 1	< 5	< 1	1.48	< 20	< 15	0.3	3.0	< 3
785	3	< 5	0.7	400	2.5	2	5	78	< 1	1.91	8	< 1	< 5	< 1	2.03	< 20	50	0.2	6.5	< 3
786	40	< 5	4.7	240	8.6	< 1	4	48	< 1	0.77	3	< 1	< 5	< 1	0.76	< 20	< 15	1.2	3.2	< 3
787	< 2	< 5	3.8	450	5.5	< 1	12	102	2	2.62	8	< 1	< 5	< 1	1.89	< 20	63	0.3	7.2	< 3
788	143	< 5	3.9	190	10.1	< 1	5	32	< 1	0.64	< 1	< 1	< 5	< 1	0.36	< 20	< 15	0.6	2.4	< 3
789	< 2	< 5	1.6	430	5.0	< 1	5	50	< 1	1.38	7	< 1	< 5	< 1	1.99	< 20	68	0.2	5.5	< 3

Neutron Activation "ID enk"

Activation Laboratories Ltd.

Report: A10-8902

1E3 - 0.5g
Aqua regia - ICP/OES

Analyte Symbol	Sn	Sr	Ta	Th	U	W	Zn	La	Ce	Nd	Sm	Eu	Tb	Yb	Lu	Mass	Ag	Cd	Cu	Mn
Unit Symbol	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	g	ppm	ppm	ppm	ppm
Detection Limit	0.02	0.05	0.5	0.2	0.5	1	50	0.5	3	5	0.1	0.2	0.5	0.2	0.05		0.2	0.5	1	S
Analysis Method	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	AR-ICP	AR-ICP	AR-ICP	AR-ICP	
679	< 0.02	< 0.05	< 0.5	2.3	< 0.5	< 1	< 50	5.9	13	9	1.2	< 0.2	< 0.5	0.4	0.06	0.526	< 0.2	0.8	44	115
680	< 0.02	< 0.05	< 0.5	4.8	1.4	< 1	< 50	14.9	32	12	2.4	0.6	< 0.5	1.2	0.14	1.840	< 0.2	< 0.5	2	74
681	< 0.02	< 0.05	< 0.5	< 0.2	< 0.5	< 1	70	1.4	< 3	< 5	0.3	< 0.2	< 0.5	< 0.2	< 0.05	0.485	< 0.2	1.4	15	1600
682	< 0.02	< 0.05	< 0.5	0.8	< 0.5	< 1	120	2.2	< 3	< 5	0.4	< 0.2	< 0.5	< 0.2	< 0.05	0.461	< 0.2	1.2	25	96
683	< 0.02	< 0.05	< 0.5	< 0.2	< 0.5	< 1	80	1.4	< 3	< 5	0.2	< 0.2	< 0.5	< 0.2	< 0.05	0.423	< 0.2	2.6	22	73
684	< 0.02	< 0.05	< 0.5	< 0.2	< 0.5	< 1	130	1.6	4	< 5	0.3	< 0.2	< 0.5	< 0.2	< 0.05	0.483	< 0.2	0.7	22	492
685	< 0.02	< 0.05	< 0.5	< 0.2	< 0.5	< 1	160	1.7	4	< 5	0.3	< 0.2	< 0.5	< 0.2	< 0.05	0.466	< 0.2	0.8	19	339
686 SAND at 687	< 0.02	< 0.05	< 0.5	5.0	1.4	< 1	70	19.0	43	15	3.5	0.9	< 0.5	1.4	0.20	1.540	< 0.2	< 0.5	9	110
687	< 0.02	< 0.05	< 0.5	1.0	< 0.5	< 1	190	3.3	5	< 5	0.5	< 0.2	< 0.5	< 0.2	< 0.05	0.478	< 0.2	0.9	25	434
688	< 0.02	< 0.05	< 0.5	0.6	< 0.5	< 1	100	2.3	5	< 5	0.4	< 0.2	< 0.5	0.3	< 0.05	0.546	< 0.2	1.0	29	281
689 Hwy showing	< 0.02	< 0.05	1.0	3.6	0.9	< 1	< 50	11.7	25	12	2.1	0.5	< 0.5	1.4	0.15	1.020	< 0.2	0.5	23	325
690 near -"	< 0.02	< 0.05	< 0.5	0.7	< 0.5	< 1	170	2.8	6	< 5	0.6	< 0.2	< 0.5	0.4	< 0.05	0.522	< 0.2	0.9	68	777
691	< 0.02	< 0.05	< 0.5	< 0.2	< 0.5	< 1	330	1.5	4	< 5	0.3	< 0.2	< 0.5	< 0.2	< 0.05	0.440	< 0.2	2.3	36	658
692	< 0.02	< 0.05	< 0.5	< 0.2	< 0.5	< 1	360	1.3	< 3	< 5	0.3	< 0.2	< 0.5	< 0.2	< 0.05	0.434	< 0.2	2.2	25	129
693	< 0.02	< 0.05	< 0.5	0.8	0.9	< 1	4190	2.0	7	< 5	0.4	< 0.2	< 0.5	0.3	< 0.05	0.445	0.3	69.6	51	1600
694	< 0.02	< 0.05	< 0.5	0.8	< 0.5	< 1	690	14.3	28	11	1.8	0.4	< 0.5	0.4	< 0.05	0.520	0.2	10.7	31	350
695	< 0.02	< 0.05	< 0.5	0.6	< 0.5	< 1	850	1.3	4	< 5	0.3	< 0.2	< 0.5	< 0.2	< 0.05	0.482	< 0.2	6.8	24	199
696	< 0.02	< 0.05	< 0.5	< 0.2	< 0.5	< 1	180	0.9	< 3	< 5	0.2	< 0.2	< 0.5	< 0.2	< 0.05	0.523	< 0.2	0.8	20	151
697	< 0.02	< 0.05	< 0.5	0.6	< 0.5	< 1	330	2.5	4	< 5	0.5	< 0.2	< 0.5	< 0.2	< 0.05	0.480	< 0.2	4.5	22	407
698	< 0.02	< 0.05	< 0.5	< 0.2	< 0.5	< 1	180	1.4	< 3	< 5	0.3	< 0.2	< 0.5	< 0.2	< 0.05	0.475	< 0.2	1.2	29	426
699	< 0.02	< 0.05	0.7	< 0.5	< 1	90	vs. bis	2.1	5	< 5	0.3	< 0.2	< 0.5	< 0.2	< 0.05	0.453	< 0.2	1.0	19	1010
700 AREAS 42 P	< 0.02	< 0.05	1.6	16.6	4.8	32 ✓	830 ✓	43.0	98	37	7.9	1.5	< 0.5	3.9	0.51	1.160	0.2	1.0	435 ✓	401 ✓
782	< 0.02	0.05	< 0.5	7.0	1.4	< 1	< 50	18.6	41	14	3.0	0.8	< 0.5	1.4	0.18	1.690				
783	< 0.02	< 0.05	< 0.5	2.3	< 0.5	< 1	80	7.7	17	< 5	1.2	0.3	< 0.5	0.4	0.06	0.719				
784	< 0.02	< 0.05	< 0.5	3.0	< 0.5	< 1	< 50	8.5	18	7	1.3	0.4	< 0.5	0.5	< 0.05	0.886				
785	< 0.02	< 0.05	< 0.5	7.2	0.9	< 1	70	18.8	38	10	2.9	0.6	< 0.5	1.2	0.17	2.080				
786	< 0.02	< 0.05	< 0.5	2.2	< 0.5	< 1	120	6.6	14	7	1.1	0.3	< 0.5	0.4	0.05	0.609				
787	< 0.02	< 0.05	0.7	5.4	1.3	< 1	< 50	15.8	35	12	2.5	0.7	< 0.5	1.4	0.15	1.580				
788	< 0.02	< 0.05	< 0.5	0.7	< 0.5	< 1	110	3.4	6	< 5	0.6	< 0.2	< 0.5	0.3	< 0.05	0.435				
789	< 0.02	< 0.05	< 0.5	4.1	0.6	< 1	< 50	13.2	29	11	2.3	0.7	< 0.5	1.1	0.13	2.060				

Certificate Of Analysis

Cattarello Assayers Inc.

Number Of Samples: 47

Client: Claim Post Resources INC.

Job: 34

Type Of Sample: 2 Pulps, 34 Core, 11 Rejects

FULVERIZED ALL, < 1 Kg, 30 g FIRE ASSAYS,
 AA FINISH, WEIGHTS SUBMITTED LISTED,
 NO REJECTS LEFT EXCEPT FEW OF 8000 Series.



Received Date: March 30, 2010

Processed Date: March 31, 2010

Report Date: April 05, 2010

Test Method: FAAA

	Au	Au-Dup		Au	Au-Dup
	AA	AA		AA	AA
	Gr/Mt	Gr/Mt		Gr/Mt	Gr/Mt
Sample ID	5	5		5	5
	=====	=====		=====	=====
	DDH #			DDH #	
1/4	51651 BLANK	>0.001 ✓		51683 CP-10-17	0.005
	51652	1.264		51684	>0.001
	51653	0.013		51685 = 51670	0.003
	51654 CP-10-12	>0.001		2/4	0.006
	51655	0.422		51686 = 51652	2.422
PROJECT	51656	0.687	0.676	8567 CP-08-10	0.024
	51657	0.146		8615	0.011
	51658	0.014		8626	0.010
CORNERS	51659 CP-10-13	0.003		8647	0.012
	51660	0.005		8648 CP-08-09	0.015
	51661 STANDARD	0.814 ✓ OK		8649	0.012
	51662 CP-10-14	0.003		8651	>0.001
	51663	0.030		8652	>0.001
	51664	>0.001		8662	>0.001
	51665	0.057		8728 CP-09-11	>0.001
4	51666 CP-10-15	>0.001		8731	>0.001
	51667	0.035			NEW YEARS LAKE WINTER 2008-2009
	51668	0.353			>0.001
	51669	0.034			
	1/4 51670	0.007			
LAKE	51671	>0.001			
2010	51672 CP-10-16	>0.001			
	51673	>0.001			
	51674	0.312			
	51675 TEST PULP	0.479 ✓ OK			
NEW YEARS MAR	51676	0.006			
FEB-MAR	51677	0.004			
	51678	0.003			
	51679 CP-10-17	>0.001			
	51680	0.004			
	51681	>0.001			
	51682	0.017			

Sample ID	DDH #	
51683 CP-10-17	0.005	
51684	>0.001	
51685 = 51670	0.003	
2/4 51686 = 51652	2.422	
8567 CP-08-10	0.024	
8615	0.011	
8626	0.010	
8647	0.012	
8648 CP-08-09	0.015	
8649	0.012	
8651	>0.001	
8652	>0.001	
8662	>0.001	
8728 CP-09-11	>0.001	
8731	>0.001	

Quality Analysis ...



Innovative Technologies

Date Submitted: 08-Apr-10
Invoice No.: A10-1568
Invoice Date: 23-Apr-10
Your Reference: 2010-B
PO Number: 2 AP 2010

CLAIM POST RESOURCES INC
39-630 RIVERPARK ROAD
TIMMINS ON P4P 1B4
Canada

ATTN: Herman Daxl

CERTIFICATE OF ANALYSIS

7 Pulp samples were submitted for analysis.

The following analytical packages were requested: Code 1C-Exp ICPOES Fire Assay ICPOES 30g
Code 4B (1-10) Major Elements Fusion ICP(WRA)
Code 4B1 Total Digestion ICP (TOTAL)
Code 4LITHO-Quant(1-10) Major Elements Fusion ICP(WRA)/Trace Elements Fusion ICP/MS(WRA4B2)

REPORT A10-1568

This report may be reproduced without our consent. If only selected portions of the report are reproduced, permission must be obtained. If no instructions were given at time of sample submittal regarding excess material, it will be discarded within 90 days of this report. Our liability is limited solely to the analytical cost of these analyses. Test results are representative only of material submitted for analysis.

Notes:

Total includes all elements in % oxide to the left of total.

Unaltered silicates and resistate minerals may not be dissolved. Values which exceed upper limit should be assayed.

CERTIFIED BY :

Emmanuel Eseme , Ph.D.
Quality Control

ACTIVATION LABORATORIES LTD.

Activation Laboratories Ltd. Report: A10-1568 rev 1

30 g Fire Assay			Activation Laboratories Ltd.										Report: A10-1568 rev 1					Li Borates Fusion					"total	
Analyte Symbol	Au	Pd	Pt	SiO2	Al2O3	Fe2O3(T)	MnO	MgO	CaO	Na2O	K2O	TiO2	P2O5	LOI	Total	Ba	Sr	Y	Sc	Zr	Be	V	Cd	C
Unit Symbol	ppb	ppb	ppb	%	%	%	%	%	%	%	%	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
Detection Limit	2	5	5	0.01	0.01	0.01	0.001	0.01	0.01	0.01	0.001	0.01	0.01	0.01	0.01	2	2	1	1	2	1	5	0.5	
Analysis Method	FA-ICP	FA-ICP	FA-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	TD-ICP	TD-ICP	
8615	40% po	3	< 5	< 5	51.94	12.14	15.86	0.136	3.78	7.22	2.46	0.62	0.706	0.16	3.69	98.71			20	< 1	1.8	33		
8728	40% popy	4	< 5	< 5	39.57	9.64	24.42	0.141	2.40	8.45	0.97	1.16	0.531	0.17	11.71	99.17			12	1	1.7	34		
51654	30% mt-il	< 2	< 5	< 5	30.52	5.31	43.64	0.126	2.38	8.74	0.55	0.10	1.285	1.73	6.13	100.5			18	< 1	2.1			
51657		132	< 5	< 5	26.20	8.45	29.02	0.206	5.16	10.36	0.07	0.51	1.378	0.36	14.04	95.75			27	< 1	2.2	47		
51671	50% po	11	< 5	< 5	26.08	5.67	36.84	0.157	4.60	9.99	0.03	0.05	0.539	0.12	6.74	90.81			16	< 1	2.0	47		
51679	60% po	4	< 5	< 5	5.54	1.45	75.06	0.035	0.88	1.32	0.04	0.03	0.083	0.04	14.72	99.20			18	< 1	2.8	26		
51684					58.37	15.05	6.98	0.133	2.56	6.36	3.60	0.54	0.750	0.19	4.85	99.37	134	188	17	16	148	< 1	108	

Activation Laboratories Ltd. Report: A10-1568 rev 4

Activation Laboratories Ltd. Report: A10-1568 rev 4

Quality Analysis ...



Innovative Technologies

Date Submitted: 08-Apr-10
Invoice No.: A10-1569
Invoice Date: 04-May-10
Your Reference: 2010-C
PO Number: 3 AP 2010

CLAIM POST RESOURCES INC
39-630 RIVERPARK ROAD
TIMMINS ON P4P 1B4
Canada

ATTN: Herman Daxl

CERTIFICATE OF ANALYSIS

28 Pulp samples were submitted for analysis.

SERIES 516.. FROM ENTIRELY PULVERIZED SAMPLES.

The following analytical packages were requested: Code 1C-Exp ICPOES Fire Assay ICPOES Au Pt Pd - 30 g assay

REPORT A10-1569 Code 1D INAA(INAA) ~ 30 g
Code 1H2 INAA(INAA) /Total Digestion ICP(TOTAL)/Total
Digestion ICP/MS INAA ~ 30 g.

This report may be reproduced without our consent. If only selected portions of the report are reproduced, permission must be obtained. If no instructions were given at time of sample submittal regarding excess material, it will be discarded within 90 days of this report. Our liability is limited solely to the analytical cost of these analyses. Test results are representative only of material submitted for analysis.

Notes:

For values exceeding the upper limits we recommend assays.

Elements which exceed the upper limits should be analyzed by assay techniques. Some elements are reported by multiple techniques. These are indicated by MULT.

Any missing data implies there wasn't sufficient sample for analysis.

CERTIFIED BY:

A handwritten signature in black ink, appearing to read "Emmanuel Eseme". Below the signature, there is a horizontal line with a small checkmark at the end.

Emmanuel Eseme , Ph.D.
Quality Control

ACTIVATION LABORATORIES LTD.

30 g Fire Assay

Activation Laboratories Ltd.

Report: A10-1569

Neutron Activation ~ 30 g

Analyte Symbol	Au	Pd	Pt	Au	Ag	Ba	Br	Ca	Co	Cr	Cs	Fe	Hf	Hg	Ir	Mo	Na	Ni	Rb	Sb	Sc	Se	Sr		
Unit Symbol	ppb	ppb	ppb	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%		
Detection Limit	2	5	5	5	5	2	100	1	1	5	10	2	0.02	1	1	5	5	0.05	50	30	0.2	0.1	5	0.05	
Analysis Method	FA-ICP	FA-ICP	FA-ICP	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA		
8567 CP-10-10	7	< 5	< 5																						
8626 CP-10-9	< 2	< 5	< 5																						
8662 CP-10-9	6	< 5	< 5																						
8731 CP-10-11	3	< 5	< 5																						
8751 TEST DAX 1	304 ✓	216 ✓	77 ✓																						
8752 TEST 745	13	< 5	< 5																						
1/4 51652 CP-10-12	1770 ✓	< 5	< 5																						
51655 CP-10-12				192	< 5	11	100	< 1	6	52	160	3	9.83	1	< 1	< 5	< 5	0.32	< 50	60	0.3	36.7	< 5	< 0.05	
51659 CP-10-13				14	< 5	10	500	6	11	24	170	< 2	6.88	1	< 1	< 5	10	0.14	< 50	70	0.3	23.7	< 5	< 0.05	
51662 CP-10-14				< 5	< 5	< 2	300	< 1	2	10	180	< 2	8.91	13	< 1	< 5	< 5	1.58	< 50	40	< 0.2	28.7	< 5	< 0.05	
51664 CP-10-15				< 5	< 5	11	200	< 1	< 1	19	240	< 2	3.20	< 1	< 1	< 5	< 5	< 0.05	< 50	40	0.8	18.8	< 5	< 0.05	
51665 CP-10-15				62	< 5	< 5																	34.1		
51667 CP-10-15				32	< 5	11	300	< 1	5	38	70	< 2	9.51	2	< 1	< 5	< 5	0.81	< 50	< 30	0.9	27.3	< 5	< 0.05	
51668 CP-10-16				315	< 5	< 5																	16.8		
51669 CP-10-16				34	< 5	< 5																	16.6		
51670 CP-10-16				12 ✓	< 5	< 5																	22.5		
51672 CP-10-16				< 2	< 5	< 5																	23.4		
51673 CP-10-17				< 2	< 5	< 5																	8.4		
51674 CP-10-17				319 ✓	< 5	< 5																	15.7		
51676 CP-10-17				4	< 5	< 5																	12.4		
51677 CP-10-17				< 5	< 5	14	200	< 1	7	142	220	< 2	7.73	2	< 1	< 5	< 5	1.16	< 50	< 30	< 0.2	13.7	< 5	< 0.05	
51678 CP-10-17				< 5	< 5	< 2	200	< 1	10	14	260	< 2	6.93	3	< 1	< 5	< 5	0.55	< 50	< 30	< 0.2	12.4	< 5	< 0.05	
51680 CP-10-17				< 2	< 5	< 5																	12.2		
51681 CP-10-17																							2.2		
51682 CP-10-17				13	< 5	< 5																	12.7		
51683 CP-10-17				< 5	< 5	< 2	300	< 1	3	24	130	< 2	4.47	3	< 1	< 5	< 5	1.39	< 50	50	< 0.2	11.4	< 5	< 0.05	
2/4 51685 ≈ 51670				24	< 5	< 2	200	< 1	4	176	160	< 2	12.8	3	< 1	< 5	< 5	0.88	< 50	< 30	< 0.2	37.3	< 5	< 0.05	
2/4 51686 ≈ 51652				2250	< 5	5	< 100	< 1	< 1	27	150	< 2	25.0	13	< 1	< 5	< 5	1.68	< 50	< 30	< 0.2	2.8	< 5	< 0.05	

2

~30g Neutron Activation Activation Laboratories Ltd. Report: A10-1569 "near total" - 4-Acid

Analyte Symbol	Sr	Ta	Th	U	W	Zn	La	Ce	Nd	Sm	Eu	Tb	Yb	Lu	Mass	Au	Ag	Cu	Cd	Mo	Pb	Ni	Zn	S
Unit Symbol	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	g	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
Detection Limit	0.1	1	0.5	0.5	4	50	1	3	5	0.1	0.2	0.5	0.2	0.05	2	0.3	1	0.3	1	3	1	1	0.01	
Analysis Method	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	MULT INAA / TD- ICP	TD-ICP	TD-ICP	TD-ICP	TD-ICP	MULT INAA / TD- ICP	MULT INAA / TD- ICP	TD-ICP	
8567																								
8626																								
8662	40% po				< 0.5				19	6	1.8				33.8	< 2	0.5	636	1.9	< 1	< 3	81	116	3.84
8731	15% popy				< 0.5				32	14	2.4				36.5	10	0.5	316	1.6	2	< 3	107	69	4.78
8751	TEST DAX1				0.5				6	< 5	0.5				32.2	252	3.3 ✓	1220 ✓	260 ✓	< 1	473 ✓	3530 ✓	20900 ✓	4.32 ✓
8752	TEST 745				< 0.5				5	< 5	0.5				48.1	12	1.6	400	2.5	1	< 3	123	44	19.0
1/4 51652	20% py				< 0.5				14	8	2.9				33.7	1670	1.8	49	2.2	< 1	< 3	33	60	11.1
51655		< 0.1	< 1	0.8	< 0.5	6	120	6	15	< 5	2.5	0.8	< 0.5	3.0	0.32	33.2								
51659		< 0.1	< 1	4.6	1.0	18	140	42	88	37	6.9	2.7	< 0.5	2.3	0.18	30.5								
51662		< 0.1	2	3.8	< 0.5	< 4	150	26	61	32	9.0	3.0	1.8	12.0	1.91	34.1								
51664		< 0.1	< 1	< 0.5	< 0.5	< 4	1300	4	10	< 5	1.4	0.9	< 0.5	1.9	0.22	34.8								
51665									25	8	4.9				30.0	69	1.9	65	118	< 1	3	7	10500	0.30
51667		< 0.1	< 1	0.9	< 0.5	< 4	4410	10	25	17	4.9	1.7	1.0	4.0	0.41	33.4								
51668	15% sl								18	10	3.4				33.3	301	2.6	78	778	< 1	< 3	6	59500	3.65
51669	10% sl								15	12	3.2				34.1	37	1.9	5	455	< 1	< 3	4	34900	2.31
1/4 51670									29	10	2.6				35.2	20	0.7	706	1.4	2	3	207	205	7.62
51672	25% pypo								25	6	2.3				33.2	< 2	0.4	315	1.8	1	4	129	136	3.22
51673	20% po								9	< 5	0.9				36.5	< 2	0.6	193	2.2	1	< 3	85	73	4.65
51674									16	10	1.9				32.1	354	22.1 > 10000	6.4	< 1	< 3	65	426	1.81	
51676									23	8	2.2				34.1	< 2	0.4	400	2.1	3	3	102	117	5.79
51677		< 0.1	< 1	1.1	0.8	< 4	90	13	25	7	2.2	1.0	< 0.5	1.6	0.18	37.1								
51678		< 0.1	< 1	1.2	< 0.5	< 4	70	13	24	9	2.1	1.0	< 0.5	1.6	0.14	33.3								
51680	15% po								16	6	1.5				36.2	10	0.5	299	2.0	1	< 3	103	42	4.89
51681	60% po								6	10	0.5				42.9	< 2	0.9	280	2.9	< 1	< 3	204	8	5.94
51682	30% popy								15	< 5	1.4				36.8	< 2	0.6	800	2.4	1	< 3	129	55	12.0
51683		< 0.1	< 1	1.0	< 0.5	< 4	370	13	25	11	2.7	0.9	< 0.5	1.5	0.19	31.3								
2/4 51685		< 0.1	< 1	1.6	< 0.5	< 4	< 50	26	49	20	4.3	1.5	< 0.5	2.7	0.42	30.6								
2/4 51686	20% py	< 0.1	2	2.0	< 0.5	9	80	4	14	< 5	2.9	1.3	0.6	5.9	0.98	35.6								

3

Mixed "TOTAL" OR N.A.

Activation Laboratories Ltd.

Report: A10-1569

Analyte Symbol	Al	As	Ba	Be	Bi	Br	Ca	Co	Cr	Cs	Fe	Ge	In	Re	Ir	K	Li	Mg	Mn	Na	P	Rb	Sb	Se
Unit Symbol	%	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppb	%	ppm	%	ppm	%	ppm	ppm	ppm	
Detection Limit	0.01	0.5	50	1	0.1	0.5	0.01	1	2	1	0.01	0.1	0.2	0.001	5	0.01	0.5	0.01	1	0.01	0.001	15	0.1	0.1
Analysis Method	TD-ICP	INAA	INAA	TD-ICP	TD-MS	INAA	TD-ICP	INAA	INAA	INAA	TD-MS	TD-MS	INAA	TD-ICP	TD-MS	TD-ICP	TD-ICP	INAA	TD-ICP	INAA	INAA	INAA	MULT INAA/TD- ICP-MS	
8567																								
8626																								
8662	4.34	< 0.5	< 50	< 1	0.4	< 0.5	5.56	55	97	< 1	21.6	1.6	< 0.2	0.003	< 5	0.04	4.0	3.29	4250	0.30	0.042	< 15	< 0.1	< 0.1
8731	3.19	4.0	330	< 1	1.4	< 0.5	4.82	30	118	< 1	16.6	0.9	< 0.2	0.004	< 5	0.52	8.1	1.35	798	0.71	0.062	< 15	< 0.1	< 0.1
8751 TEST DAX1	1.03	3.6	< 50	< 1	1.3	< 0.5	0.82	182 ✓	125	< 1	5.41 ✓	0.6	< 0.2	0.017	< 5	0.45	3.2	0.46	528	0.11	0.008	24	0.7	< 0.1
8752 TEST 745	0.60	< 0.5	< 50	< 1	2.0	< 0.5	1.88	35	13	2	33.8	1.3	< 0.2	0.003	< 5	0.05	< 0.5	1.50	2000	0.08	0.007	< 15	< 0.1	< 0.1
1/4 51652	4.82	7.6	< 50	< 1	0.5	< 0.5	0.78	40	13	2	24.9	1.0	< 0.2	0.007	< 5	1.28	4.8	0.76	404	1.22	0.011	< 15	0.2	8.0
51655																								
51659																								
51662																								
51664																								
51665	5.09	27.9	500	1	1.0	< 0.5	5.49	46	58	< 1	11.1	0.7	< 0.2	0.001	< 5	1.23	8.1	2.18	2610	0.40	0.222	< 15	0.2	< 0.1
51667																								
51668	3.63	5.4	< 50	< 1	0.3	< 0.5	6.32	75	43	< 1	9.14	0.7	0.8	< 0.001	< 5	0.10	7.2	1.61	2020	0.44	0.296	< 15	0.3	8.5
51669	3.90	6.8	< 50	< 1	0.3	< 0.5	11.1	58	46	< 1	9.91	0.8	0.4	< 0.001	< 5	0.26	11.2	3.06	2420	0.19	0.267	< 15	0.6	6.0
1/4 51670	6.54	< 0.5	140	< 1	7.2	< 0.5	3.68	238	159	< 1	13.0	0.8	< 0.2	0.002	< 5	0.36	6.4	1.92	945	1.24	0.053	< 15	< 0.1	< 0.1
51672	5.87	< 0.5	160	< 1	2.7	< 0.5	1.64	167	69	< 1	16.4	1.2	0.3	0.002	< 5	0.27	8.6	4.41	1960	0.09	0.044	< 15	0.2	< 0.1
51673	3.15	< 0.5	< 50	< 1	1.4	< 0.5	6.12	49	104	< 1	26.6	1.1	< 0.2	0.004	< 5	0.02	7.9	2.25	1750	0.01	0.023	< 15	< 0.1	< 0.1
51674	4.06	45.0	< 50	< 1	3.9	< 0.5	5.76	81	180	< 1	11.1	1.2	1.2	0.002	< 5	< 0.01	6.2	2.19	1750	0.47	0.041	< 15	0.2	< 0.1
51676	1.95	18.8	< 50	< 1	0.3	< 0.5	6.03	108	345	< 1	14.8	1.6	< 0.2	< 0.001	< 5	0.13	3.7	1.01	837	0.50	0.052	< 15	0.3	< 0.1
51677																								
51678																								
51680	3.98	4.3	< 50	< 1	0.6	< 0.5	3.28	26	223	< 1	23.9	0.9	< 0.2	0.004	< 5	0.47	3.8	1.17	621	1.29	0.030	< 15	< 0.1	< 0.1
51681	0.41	< 0.5	< 50	< 1	1.5	< 0.5	0.40	62	102	< 1	51.4	1.7	< 0.2	0.004	< 5	0.09	< 0.5	0.11	81	0.06	0.004	< 15	< 0.1	< 0.1
51682	3.20	< 0.5	< 50	< 1	2.4	< 0.5	0.94	87	236	< 1	30.5	1.1	< 0.2	0.004	< 5	0.02	5.6	1.36	534	0.94	0.030	< 15	< 0.1	< 0.1
51683																								
2/4 51685 = 51670																								
2/4 51686 = 51652																								

4

Mixed "TOTAL" OR N.A.

Activation Laboratories Ltd.

Report: A10-1569

Analyte Symbol	Sn	Sr	Ta	Te	Ti	Th	Tl	V	W	Y	La	Eu	Tb	Yb	Lu
Unit Symbol	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Detection Limit	1	1	0.5	0.1	0.01	0.2	0.1	2	1	1	0.5	0.2	0.5	0.2	0.05
Analysis Method	TD-MS	TD-ICP	INAA	TD-MS	TD-ICP	INAA	TD-MS	TD-ICP	INAA	TD-ICP	INAA	INAA	INAA	INAA	INAA
8567															
8626															
8662	1	109	< 0.5	0.2	0.27	0.9	< 0.1	98	< 1	21	9.0	0.7	< 0.5	2.0	0.38
8731	< 1	107	< 0.5	0.5	0.17	1.5	0.1	53	< 1	13	17.4	0.8	< 0.5	1.4	0.26
8751 TEST DAX1	< 1	19	< 0.5	0.3	0.07	1.3	0.1	19	< 1	7	3.7	< 0.2	< 0.5	0.5	0.13
8752 TEST 745	< 1	12	< 0.5	0.4	0.05	0.4	< 0.1	29	< 1	8	2.5	0.3	< 0.5	0.5	0.11
1/4 51652	3	22	< 0.5	0.6	0.40	2.5	0.2	483	24	17	4.0	1.2	0.6	5.3	0.96
51655															
51659															
51662															
51664															
51665	< 1	45	< 0.5	< 0.1	0.26	0.4	0.1	27	< 1	39	10.4	2.0	0.8	4.0	0.51
51667															
51668	1	38	< 0.5	< 0.1	0.45	0.6	< 0.1	31	< 1	45	7.2	1.4	0.6	2.8	0.35
51669	1	81	0.7	< 0.1	0.33	0.4	< 0.1	20	< 1	47	5.5	1.3	0.7	3.0	0.29
1/4 51670	2	197	< 0.5	0.6	0.36	0.6	< 0.1	129	< 1	22	14.7	0.9	< 0.5	1.9	0.28
51672	4	80	0.8	0.3	0.27	1.7	< 0.1	117	< 1	32	13.1	0.8	< 0.5	2.8	0.54
51673	1	76	< 0.5	0.3	0.14	< 0.2	< 0.1	81	< 1	11	5.3	0.4	< 0.5	1.0	0.16
51674	5	122	< 0.5	0.2	0.28	< 0.2	< 0.1	103	3	9	8.1	0.7	0.6	1.4	0.15
51676	2	243	0.8	0.3	0.31	1.1	< 0.1	94	< 1	9	12.0	0.8	< 0.5	1.6	0.20
51677															
51678															
51680	1	65	< 0.5	0.3	0.19	< 0.2	0.1	71	< 1	13	8.8	0.6	< 0.5	1.2	0.21
51681	< 1	9	< 0.5	0.3	0.02	< 0.2	< 0.1	22	< 1	2	5.6	< 0.2	< 0.5	0.2	< 0.05
51682	< 1	37	< 0.5	0.3	0.22	1.1	< 0.1	69	< 1	15	7.5	0.5	< 0.5	1.2	0.17
51683															
2/4 51685 = 51670															
2/4 51686 = 51652															

30 g F.A. for RHODIUM

Report Date: 4/26/2010

Analyte Symbol	Rh	DDH
Unit Symbol	ppb	NEW YEARS LAKE
Detection Limit	5	
Analysis Method	FA-MS	
8753 SULFIDE BLANK	<5 ✓	EXCAVUS 753
8754 TEST PULP DAXL	69 ✓	—
8755 = 8615	<5	CP-08-9
8756 = 8662	<5	CP-09-11
8757 = 8728	<5	CP-10-12
8758 = 8731	<5	CP-10-15
8759 = 51654	<5	CP-10-16
8760 = 51657	<5	CP-10-17
8761 = 51668	<5	
8762 = 51671	<5	
8763 = 51672	<5	
8764 = 51673	<5	
8765 = 51679	<5	
8766 = 51681	<5	
8767 = 51682	<5	
8768 TEST PULP JAMS412	<5 ✓	

FROM <1kg PULPS FROM REJECTS

PULPS
FROM ENTIRELY
PULVERIZED
NQ CORE SAMPLES.

Quality Control

Analyte Symbol	Rh
Unit Symbol	ppb
Detection Limit	5
Analysis Method	FA-MS
WMS-1 Meas	211
WMS-1 Cert	225
8762 Orig = 51671	<5
8762 Dup	<5
Method Blank Method	<5
Blank	

Quality Analysis ...



Innovative Technologies

Date Submitted: 30-Sep-10
Invoice No.: A10-6840
Invoice Date: 03-Nov-10
Your Reference: CP12-DAXL

CLAIM POST RESOURCES INC
39-630 RIVERPARK ROAD
TIMMINS ON P4P 1B4
Canada

ATTN: Herman Daxl

CERTIFICATE OF ANALYSIS

9 Crushed Rock samples were submitted for analysis. left over rejects of A10-5875

The following analytical package was requested Code 1C-OES Fire Assay ICPOES 30 g

REPORT **A10-6840**

CP - 10 - 12

This report may be reproduced without our consent. If only selected portions of the report are reproduced, permission must be obtained. If no instructions were given at time of sample submittal regarding excess material, it will be discarded within 90 days of this report. Our liability is limited solely to the analytical cost of these analyses. Test results are representative only of material submitted for analysis.

Notes:

CERTIFIED BY :

A handwritten signature in black ink, appearing to read "Emmanuel Eseme". It is positioned above a horizontal line.

Emmanuel Eseme , Ph.D.
Quality Control

ACTIVATION LABORATORIES LTD.

1336 Sandhill Drive, Ancaster, Ontario Canada L9G 4V5 TELEPHONE +1.905.648.9611 or
+1.888.228.5227 FAX +1.905.648.9613
E-MAIL ancaster@actlabsint.com ACTLABS GROUP WEBSITE <http://www.actlabsint.com>

30 g Fire Assay

Activation Laboratories Ltd. Report: A10-6840 rev 2

Analyte Symbol	Au	Pd	Pt
Unit Symbol	ppb	ppb	ppb
Detection Limit	2	5	5
Analysis Method	FA-ICP	FA-ICP	FA-ICP
51928	17	< 5	< 5
51938	37	< 5	< 5
51945	10	< 5	< 5
51954	107	< 5	< 5
51963	10	< 5	< 5
51976	109	< 5	< 5
51979	< 2	< 5	< 5
51985	< 2	< 5	< 5
51991	< 2	< 5	< 5

Activation Laboratories Ltd. Report: A10-6840 rev 2

Quality Control			
Analyte Symbol	Au	Pd	Pt
Unit Symbol	ppb	ppb	ppb
Detection Limit	2	5	5
Analysis Method	FA-ICP	FA-ICP	FA-ICP
CDN-PGMS-18 Meas	536.00	1470.00	329.00
CDN-PGMS-18 Cert	517.00	1420.00	329.00
CDN-PGMS-18 Meas	516.00	1440.00	306.00
CDN-PGMS-18 Cert	517.00	1420.00	329.00
51945 Orig	10.00	< 5	< 5
51945 Split	13.00	< 5	< 5
51991 Orig	< 2	< 5	< 5
51991 Dup	< 2	< 5	< 5

Quality Analysis ...



Innovative Technologies

Date Submitted: 07-Sep-10

Invoice No.: A10-5875

Invoice Date: 28-Oct-10

Your Reference: CP12-DAXL

CLAIM POST RESOURCES INC
39-630 RIVERPARK ROAD
TIMMINS ON P4P 1B4
Canada

ATTN: Herman Daxl

CERTIFICATE OF ANALYSIS

86 CORE
4 PULP

90 Rock samples were submitted for analysis. Fine crush 90% <2 mm, made 250 g pulp 95% <105 µm

The following analytical packages were request

ed:

REPORT **A10-5875**

Code 1D INAA(INAAGEO) ~ 30 g

Code 1F2 Total Digestion ICP(TOTAL)

Code 4LITHO (11+) Major Elements Fusion ICP(WRA)/Trace Elements Fusion ICP/MS(WRA 4B2)

ALL OF CP-10-12

This report may be reproduced without our consent. If only selected portions of the report are reproduced, permission must be obtained. If no instructions were given at time of sample submittal regarding excess material, it will be discarded within 90 days of this report. Our liability is limited solely to the analytical cost of these analyses. Test results are representative only of material submitted for analysis.

Notes:

We recommend using option 4B1 for accurate levels of the base metals Cu, Pb, Zn, Ni and Ag. Option 4B-INAA for As, Sb, high W >100ppm, Cr>1000ppm and Sn >50ppm by Code 5D. Values for these elements provided by Fusion ICP/MS, are order of magnitude only and are provided for general information. Mineralized samples should have the Quant option selected or request assays for values which exceed the range of option 4B1. Total includes all elements in % oxide to the left of total.

For values exceeding the upper limits we recommend assays.

Values which exceed the upper limit should be assayed for accurate numbers.

CERTIFIED BY :

Emmanuel Eseme , Ph.D.

Quality Control

ACTIVATION LABORATORIES LTD.

Activation Laboratories Ltd.

Report: A10-5875 rev 1

~ 30 g neutron activation

Analyte Symbol	Au	Ag	As	Ba	Br	Ca	Co	Cr	Cs	Fe	Hf	Hg	Ir	Mo	Na	Ni	Rb	Sb	Sc	Se
Unit Symbol	ppb	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	%	ppm	ppm	ppm	ppm	ppm
Detection Limit	5	5	2	100	1	1	5	10	2	0.02	1	1	5	5	0.05	50	30	0.2	0.1	5
Analysis Method	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA
51909	< 5	< 5	10	400	< 1	4	45	70	< 2	8.29	3	< 1	< 5	< 5	1.20	< 50	< 30	< 0.2	31.7	< 5
51910	< 5	< 5	8	600	< 1	8	63	50	< 2	10.10	2	< 1	< 5	< 5	1.49	< 50	< 30	< 0.2	38.8	< 5
51911	< 5	< 5	5	< 100	< 1	4	71	< 10	< 2	13.00	4	< 1	< 5	< 5	0.73	< 50	< 30	< 0.2	45.8	< 5
51912	29	< 5	5	< 100	< 1	8	56	90	< 2	10.30	2	< 1	< 5	< 5	0.70	< 50	< 30	< 0.2	31.0	< 5
51913	< 5	< 5	4	< 100	< 1	7	35	80	< 2	7.54	2	< 1	< 5	< 5	0.67	< 50	< 30	< 0.2	29.9	< 5
51914	< 5	< 5	3	< 100	< 1	16	30	70	< 2	7.99	< 1	< 1	< 5	< 5	0.29	< 50	< 30	< 0.2	21.3	< 5
51915	< 5	< 5	6	500	< 1	6	30	70	< 2	6.32	< 1	< 1	< 5	< 5	0.92	< 50	< 30	< 0.2	26.2	< 5
51916	< 5	< 5	7	< 100	< 1	9	37	70	< 2	6.90	< 1	< 1	< 5	< 5	0.52	< 50	60	< 0.2	29.0	< 5
51917	< 5	< 5	< 2	400	< 1	3	13	80	< 2	3.99	2	< 1	< 5	< 5	0.25	< 50	80	< 0.2	15.3	< 5
51918	< 5	< 5	< 2	< 100	< 1	< 1	38	70	< 2	7.17	2	< 1	< 5	< 5	2.61	< 50	< 30	< 0.2	32.1	< 5
STAND. 51919 OREAS H3	2100 ✓	< 5	7 ✓	< 100	< 1	< 1	20 ✓	140	< 2	4.57	3 ✓	< 1	< 5	27 ✓	0.17	< 50	< 30	15.3 ✓	11.1 ✓	< 5
51920	10	< 5	< 2	< 100	< 1	10	34	50	< 2	6.47	2	< 1	< 5	< 5	< 0.05	< 50	< 30	< 0.2	27.2	< 5
51921	< 5	< 5	< 2	< 100	< 1	6	47	40	< 2	8.80	2	< 1	< 5	< 5	1.98	< 50	< 30	< 0.2	31.5	< 5
51922	< 5	< 5	< 2	300	< 1	6	26	30	< 2	7.70	5	< 1	< 5	< 5	0.71	< 50	< 30	0.4	18.8	< 5
51923	< 5	< 5	< 2	400	< 1	< 1	7	20	< 2	2.63	12	< 1	< 5	< 5	2.43	< 50	< 30	< 0.2	3.0	< 5
51924	52	< 5	29	< 100	< 1	4	45	90	< 2	8.77	< 1	< 1	< 5	< 5	0.78	< 50	60	0.5	32.9	< 5
51925	< 5	< 5	5	< 100	< 1	< 1	17	50	< 2	5.79	10	< 1	< 5	10	1.94	< 50	< 30	< 0.2	12.7	< 5
51926	< 5	< 5	< 2	< 100	< 1	< 1	8	30	< 2	3.59	16	< 1	< 5	< 5	2.81	< 50	< 30	< 0.2	2.6	< 5
51927	< 5	< 5	< 2	< 100	< 1	< 1	10	30	< 2	4.25	16	< 1	< 5	< 5	2.92	< 50	60	< 0.2	3.5	< 5
51928	28	< 5	< 2	< 100	< 1	< 1	9	40	< 2	5.08	16	< 1	< 5	< 5	3.40	< 50	< 30	< 0.2	1.7	< 5
51929	183	< 5	7	< 100	< 1	< 1	76	< 10	< 2	16.20	28	< 1	< 5	10	0.74	< 50	< 30	< 0.2	4.2	9
51930	< 5	< 5	< 2	< 100	< 1	< 1	6	40	< 2	3.31	15	< 1	< 5	< 5	3.05	< 50	< 30	< 0.2	2.9	< 5
51931	2090	< 5	10	400	< 1	4	59	30	< 2	17.80	16	< 1	< 5	< 5	2.18	< 50	< 30	< 0.2	4.6	15
51932	< 5	< 5	< 2	400	< 1	6	50	100	< 2	10.50	2	< 1	< 5	< 5	2.06	< 50	60	< 0.2	39.4	< 5
STAND. 51933 OREAS 54Pa	2830 ✓	< 5	9 ✓	700	< 1	< 1	19	40	< 2	7.44	2	< 1	< 5	13	2.28	< 50	< 30	2.1	11.3 ✓	16
51934	< 5	< 5	< 2	< 100	< 1	7	34	60	< 2	7.87	2	< 1	< 5	< 5	1.55	< 50	50	0.6	29.8	< 5
51935	< 5	< 5	< 2	< 100	< 1	5	55	30	< 2	13.50	2	< 1	< 5	< 5	1.69	< 50	< 30	0.6	41.1	< 5
51936 much mt	< 5	< 5	< 2	< 100	< 1	6	40	20	< 2	29.40	< 1	< 1	< 5	< 5	0.15	< 50	50	0.5	23.6	< 5
51937 much mt	< 5	< 5	< 2	< 100	< 1	4	30	10	< 2	46.20	< 1	< 1	< 5	< 5	< 0.05	< 50	40	< 0.2	3.9	< 5
51938 90% mt	< 5	< 5	< 2	< 100	< 1	4	31	< 10	< 2	49.70	< 1	< 1	< 5	< 5	< 0.05	< 50	< 30	< 0.2	4.3	< 5

Activation Laboratories Ltd.

Report: A10-5875 rev 1

~ 30 g neutron activation

Analyte Symbol	Au	Ag	As	Ba	Br	Ca	Co	Cr	Cs	Fe	Hf	Hg	Ir	Mo	Na	Ni	Rb	Sb	Sc	Se
Unit Symbol	ppb	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	%	ppm	ppm	ppm	ppm	
Detection Limit	5	5	2	100	1	1	5	10	2	0.02	1	1	5	5	0.05	50	30	0.2	0.1	
Analysis Method	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	
51939	< 5	< 5	< 2	< 100	< 1	6	51	40	< 2	17.90	1	< 1	< 5	< 5	1.25	< 50	60	< 0.2	34.0	< 5
51940	< 5	< 5	8	< 100	< 1	9	46	10	< 2	25.50	< 1	< 1	< 5	< 5	< 0.05	< 50	< 30	< 0.2	62.6	< 5
51941	63	< 5	155	< 100	3	6	59	< 10	< 2	16.00	< 1	< 1	< 5	7	0.05	< 50	< 30	0.4	29.4	< 5
51942	< 5	< 5	21	< 100	< 1	5	58	30	< 2	21.00	2	< 1	< 5	< 5	0.08	< 50	< 30	< 0.2	33.0	< 5
51943	41	< 5	64	400	5	9	57	30	< 2	18.10	1	< 1	< 5	< 5	0.08	< 50	< 30	0.9	25.1	< 5
51944	50	< 5	131	< 100	< 1	5	77	30	< 2	16.40	2	< 1	< 5	< 5	0.08	< 50	50	1.7	22.8	< 5
51945	< 5	< 5	15	< 100	< 1	4	68	30	< 2	15.10	2	< 1	< 5	< 5	0.08	< 50	< 30	0.6	33.9	< 5
51946	119	< 5	178	< 100	8	9	48	30	< 2	14.10	1	< 1	< 5	< 5	0.05	< 50	< 30	0.5	19.0	< 5
51947	< 5	< 5	8	< 100	< 1	9	53	50	< 2	10.20	2	< 1	< 5	< 5	1.89	< 50	< 30	0.5	40.0	< 5
51948	< 5	< 5	6	600	< 1	8	49	60	< 2	9.20	2	< 1	< 5	< 5	2.02	< 50	< 30	< 0.2	33.2	< 5
51949	< 5	< 5	< 2	< 100	< 1	6	50	30	< 2	9.85	2	< 1	< 5	< 5	1.72	< 50	50	< 0.2	37.0	< 5
51950	< 5	< 5	< 2	< 100	2	8	54	40	< 2	10.30	< 1	< 1	< 5	< 5	2.15	< 50	< 30	< 0.2	40.0	< 5
51951	85	< 5	< 2	< 100	< 1	5	45	30	< 2	22.60	< 1	< 1	< 5	< 5	1.40	< 50	< 30	< 0.2	27.6	< 5
51952	< 5	< 5	< 2	< 100	< 1	4	45	30	< 2	10.40	2	< 1	< 5	< 5	2.16	< 50	< 30	< 0.2	37.2	< 5
51953	< 5	< 5	< 2	< 100	< 1	5	42	20	< 2	12.20	1	< 1	< 5	< 5	1.81	< 50	< 30	< 0.2	33.2	< 5
51954	< 5	< 5	< 2	< 100	< 1	7	29	30	< 2	9.16	< 1	< 1	< 5	< 5	1.71	< 50	< 30	0.5	31.6	< 5
51955	19	< 5	< 2	< 100	< 1	6	37	30	< 2	9.32	2	< 1	< 5	< 5	1.17	< 50	< 30	< 0.2	32.4	< 5
51956	< 5	< 5	9	< 100	< 1	6	44	30	< 2	9.86	< 1	< 1	< 5	< 5	1.57	< 50	< 30	< 0.2	32.5	< 5
51957	< 5	< 5	10	< 100	< 1	6	43	< 10	< 2	12.90	< 1	< 1	< 5	< 5	0.47	< 50	< 30	0.7	23.5	< 5
51958	17	< 5	22	< 100	< 1	10	33	20	< 2	9.35	< 1	< 1	< 5	< 5	0.13	< 50	< 30	< 0.2	25.3	< 5
51959	108	< 5	< 2	< 100	< 1	8	24	50	< 2	5.77	< 1	< 1	< 5	< 5	0.24	< 50	40	< 0.2	25.6	< 5
STAND. 0% As 50% Pb	812 ✓	< 5	10 ✓	600 ✓	< 1	< 1	13	40	< 2	4.69	3	< 1	< 5	< 5	2.77	< 50	< 30	1.5	10.3	< 5
51961	< 5	< 5	< 2	600	< 1	7	33	70	< 2	8.12	1	< 1	< 5	< 5	0.67	< 50	70	< 0.2	33.2	< 5
51962	82	< 5	< 2	500	< 1	8	40	60	< 2	8.26	1	< 1	< 5	< 5	0.40	< 50	120	< 0.2	32.5	< 5
51963	28	< 5	< 2	< 100	< 1	7	51	110	2	10.70	2	< 1	< 5	< 5	1.61	< 50	< 30	< 0.2	42.6	< 5
51964	119	< 5	3	< 100	< 1	4	39	110	< 2	7.70	1	< 1	< 5	< 5	0.72	< 50	< 30	< 0.2	30.9	< 5
51965	143	< 5	4	< 100	< 1	6	45	130	< 2	9.74	1	< 1	< 5	< 5	1.44	< 50	50	< 0.2	38.3	< 5
51966	< 5	< 5	< 2	< 100	< 1	5	55	120	< 2	10.10	2	< 1	< 5	< 5	1.24	< 50	< 30	< 0.2	38.8	< 5
51967	< 5	< 5	< 2	< 100	< 1	6	55	120	< 2	10.00	2	< 1	< 5	< 5	0.65	< 50	40	< 0.2	39.0	< 5
51968	< 5	< 5	5	< 100	< 1	5	60	140	< 2	10.80	2	< 1	< 5	< 5	1.12	< 50	< 30	< 0.2	42.4	< 5

Activation Laboratories Ltd.

Report: A10-5875 rev 1

~30 g neutron activation

Analyte Symbol	Au	Ag	As	Ba	Br	Ca	Co	Cr	Cs	Fe	Hf	Hg	Ir	Mo	Na	Ni	Rb	Sb	Sc	Se
Unit Symbol	ppb	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	%	ppm	ppm	ppm	ppm	
Detection Limit	5	5	2	100	1	1	5	10	2	0.02	1	1	5	5	0.05	50	30	0.2	0.1	
Analysis Method	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA								
51969	<5	<5	<2	<100	<1	5	54	130	<2	10.40	1	<1	<5	<5	1.29	<50	<30	<0.2	40.8	<5
51970	149	<5	11	<100	<1	6	44	110	<2	8.51	<1	<1	<5	<5	0.37	<50	<30	<0.2	32.3	<5
51971	<5	<5	9	<100	<1	5	53	110	<2	9.12	<1	<1	<5	<5	0.89	<50	70	<0.2	37.0	<5
51972	<5	<5	<2	<100	<1	4	49	120	<2	10.80	2	<1	<5	<5	0.90	<50	<30	0.5	41.9	<5
51973	157	<5	9	<100	<1	6	58	120	<2	9.68	2	<1	<5	<5	0.58	<50	40	0.8	37.8	<5
51974	207	<5	6	<100	<1	4	58	140	<2	10.60	1	<1	<5	<5	1.57	<50	60	<0.2	42.7	<5
51975	270	<5	11	<100	<1	5	63	130	<2	11.10	<1	<1	<5	<5	0.72	<50	70	0.4	43.0	<5
51976	187	<5	16	<100	<1	8	48	120	3	10.60	2	<1	<5	<5	1.75	<50	<30	<0.2	39.2	<5
51977	318	<5	6	<100	<1	8	51	100	<2	13.00	<1	<1	<5	<5	2.12	<50	<30	<0.2	29.3	<5
51978	<5	<5	3	<100	<1	4	31	90	<2	7.01	1	<1	<5	<5	2.40	<50	<30	0.5	28.0	<5
51979	<5	<5	<2	<100	<1	6	49	90	<2	12.60	2	<1	<5	<5	2.04	<50	<30	<0.2	36.4	<5
51980	35	<5	6	400	<1	10	56	20	<2	11.60	2	<1	<5	<5	0.51	<50	<30	<0.2	31.5	<5
51981	<5	<5	<2	<100	<1	9	39	30	<2	8.34	2	<1	<5	<5	0.58	<50	90	<0.2	31.4	<5
51982	<5	<5	<2	500	<1	5	36	40	<2	7.19	2	<1	<5	<5	0.44	<50	<30	<0.2	28.2	<5
STAND. 51983 OREAS 13 hr	228✓	<5	62✓	1000	<1	6✓	81✓	10800✓	8	8.47✓	3	<1	18✓	<5	1.79✓	2070 ^{v5} ₂₂₄₇	130	2.6	25.4	<5
51984	12	<5	<2	600	<1	6	46	100	<2	10.40	2	<1	<5	<5	0.18	<50	70	<0.2	38.2	<5
51985	<5	<5	<2	<100	<1	9	45	110	<2	9.29	2	<1	<5	<5	1.50	<50	<30	<0.2	35.2	<5
51986	<5	<5	<2	<100	<1	10	49	130	<2	9.74	2	<1	<5	<5	0.77	<50	<30	<0.2	41.0	<5
51987	<5	<5	<2	<100	<1	7	30	70	<2	6.78	<1	<1	<5	<5	2.33	<50	<30	<0.2	27.2	<5
51988	<5	<5	<2	500	<1	8	37	30	<2	15.70	<1	<1	<5	<5	0.50	<50	60	0.4	19.5	<5
51989	92	<5	6	300	1	5	37	60	<2	7.02	<1	<1	<5	<5	0.38	<50	<30	<0.2	23.1	<5
51990	14	<5	8	<100	<1	5	48	40	<2	13.50	<1	<1	<5	<5	0.64	<50	<30	<0.2	29.4	<5
51991	<5	<5	<2	400	<1	7	52	50	<2	9.08	<1	<1	<5	<5	0.50	<50	<30	<0.2	29.0	<5
51992	<5	<5	<2	300	<1	4	43	110	<2	9.02	2	<1	<5	<5	1.67	<50	<30	0.3	34.8	<5
51993	<5	<5	5	<100	<1	6	39	120	<2	8.19	2	<1	<5	<5	1.59	<50	<30	<0.2	33.3	<5
51994	284	<5	8	<100	<1	6	35	110	2	9.72	2	<1	<5	<5	1.92	<50	<30	<0.2	34.2	<5
51995	<5	<5	<2	<100	<1	5	49	110	<2	9.04	2	<1	<5	<5	2.25	<50	<30	<0.2	38.0	<5
51996	<5	<5	<2	<100	<1	5	53	120	<2	9.77	2	<1	<5	<5	1.37	<50	<30	<0.2	38.8	<5
51997	<5	<5	<2	<100	<1	4	51	110	<2	10.30	<1	<1	<5	<5	2.00	<50	<30	<0.2	39.3	<5
51998	<5	<5	3	<100	<1	8	39	50	<2	7.80	<1	<1	<5	<5	0.07	<50	<30	<0.2	27.4	<5

Activation Laboratories Ltd.

Report: A10-5875 rev 1

Analyte Symbol	Sn	Sr	Ta	Th	U	W	Zn	La	Ce	Nd	Sm	Eu	Tb	Yb	Lu	Mass	Ag	Al	As	Ba	
Unit Symbol	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	g	ppm	%	ppm	ppm	
Detection Limit	0.05	0.1	1	0.5	0.5	4	50	1	3	5	0.1	0.2	0.5	0.2	0.05		0.3	0.01	3	7	
Analysis Method	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	TD-ICP	TD-ICP	TD-HCP	TD-ICP		
51909	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	6	12	< 5	2.2	1.0	< 0.5	3.2	0.47	32.8					
51910	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	220	4	14	< 5	1.9	0.8	< 0.5	3.2	0.54	34.5					
51911	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	270	7	21	< 5	3.1	1.1	< 0.5	5.2	0.73	33.7					
51912	< 0.05	< 0.1	< 1	< 0.5	2.3	< 4	120	3	< 3	< 5	1.1	0.6	< 0.5	2.2	0.25	33.6					
51913	< 0.05	< 0.1	< 1	1.0	< 0.5	< 4	120	5	11	< 5	2.0	1.1	< 0.5	2.1	0.09	32.5					
51914	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	130	4	< 3	11	1.7	1.0	< 0.5	1.7	0.33	31.9					
51915	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	3	8	< 5	1.4	0.6	< 0.5	1.9	< 0.05	33.4					
51916	< 0.05	< 0.1	< 1	< 0.5	< 0.5	9	< 50	3	10	< 5	1.5	0.6	< 0.5	2.4	0.36	30.2					
51917	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	3	11	6	1.5	0.8	< 0.5	2.0	0.28	28.8					
51918	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	4	10	< 5	1.8	0.9	< 0.5	2.5	0.41	30.2					
STAND. 51919 OREAS #3	< 0.05	< 0.1	< 1	5.7 ✓	< 0.5	35	2250 2083	4	8 ✓	< 5	0.7 ✓	< 0.2	< 0.5	< 0.2	< 0.05	25.9					
51920	< 0.05	< 0.1	< 1	1.0	< 0.5	< 4	90	5	22	10	2.9	1.1	< 0.5	3.5	0.22	31.7					
51921	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	140	4	11	< 5	1.8	0.8	< 0.5	2.8	0.16	32.9					
51922	< 0.05	< 0.1	< 1	1.4	< 0.5	< 4	< 50	3	13	12	1.9	1.0	< 0.5	3.8	0.40	34.1					
51923	< 0.05	< 0.1	< 1	6.6	< 0.5	< 4	< 50	20	39	10	3.7	1.3	< 0.5	5.1	0.85	30.2					
51924	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	7	18	12	2.3	0.8	< 0.5	3.0	0.29	31.3					
51925	< 0.05	< 0.1	< 1	4.9	< 0.5	6	130	6	15	< 5	2.5	1.2	< 0.5	4.7	0.73	30.4					
51926	< 0.05	< 0.1	< 1	6.6	< 0.5	5	< 50	5	12	15	2.2	0.9	0.9	4.6	0.80	30.4					
51927	< 0.05	< 0.1	< 1	6.4	< 0.5	< 4	< 50	4	21	< 5	1.9	1.0	< 0.5	4.4	0.86	31.8					
51928	< 0.05	< 0.1	< 1	6.5	< 0.5	< 4	< 50	7	22	< 5	2.9	1.2	< 0.5	5.4	0.83	30.5					
51929	< 0.05	< 0.1	< 1	9.6	2.6	8	200	7	21	< 5	2.9	1.7	< 0.5	7.1	1.50	32.5	5.4	7.68	< 3	165	
51930	< 0.05	< 0.1	< 1	7.0	< 0.5	8	< 50	5	20	< 5	2.4	1.2	< 0.5	4.3	0.72	31.2					
51931	< 0.05	< 0.1	< 1	5.0	< 0.5	< 4	< 50	7	22	15	3.7	1.6	< 0.5	5.9	0.92	35.8	5.2	5.24	< 3	32	
STAND. 51933 OREAS 549a	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	121	11 ✓	22 ✓	< 5	1.8	< 0.2	< 0.5	1.7	0.23 ✓	30.0				
51934	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	4	< 3	5	2.0	0.9	< 0.5	2.7	0.43	32.5					
51935	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	130	7	19	< 5	2.6	1.3	< 0.5	3.2	0.28	31.3					
51936	< 0.05	< 0.1	< 1	2.7	< 0.5	< 4	< 50	64	152	59	14.9	2.2	2.1	10.1	1.13	34.2	< 0.3	2.81	10	14	
51937	< 0.05	< 0.1	< 1	1.8	< 0.5	< 4	< 50	11	26	7	2.4	0.5	< 0.5	1.9	0.27	47.1	0.4	0.64	< 3	34	
51938	< 0.05	< 0.1	< 1	2.1	< 0.5	< 4	< 50	51	112	37	10.0	1.1	1.6	5.8	0.78	49.6	0.4	0.48	9	31	

4 acid digest

Activation Laboratories Ltd. Report: A10-5875 rev 1

4 acid digest

Analyte Symbol	Sn	Sr	Ta	Th	U	W	Zn	La	Ce	Nd	Sm	Eu	Tb	Yb	Lu	Mass	Ag	Al	As	Ba
Unit Symbol	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	g	ppm	%	ppm	ppm
Detection Limit	0.05	0.1	1	0.5	0.5	4	50	1	3	5	0.1	0.2	0.5	0.2	0.05		0.3	0.01	3	7
Analysis Method	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	TD-ICP	TD-ICP	TD-ICP	TD-ICP	
51939	< 0.05	< 0.1	< 1	1.0	< 0.5	< 4	100	4	13	< 5	1.8	0.6	< 0.5	2.8	0.21	34.0	0.3	4.62	4	63
51940	< 0.05	< 0.1	< 1	< 0.5	3.2	< 4	< 50	13	42	16	6.9	0.8	< 0.5	11.1	1.69	35.5				
51941	< 0.05	< 0.1	< 1	1.6	< 0.5	< 4	< 50	9	28	21	4.9	1.0	1.6	5.8	0.65	33.3				
51942	< 0.05	< 0.1	< 1	1.4	< 0.5	< 4	140	6	14	< 5	3.1	0.9	< 0.5	4.4	0.39	33.4				
51943	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	10	25	< 5	4.1	1.2	< 0.5	3.6	0.62	30.2				
51944	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	80	5	15	15	2.6	1.0	< 0.5	3.3	0.32	33.0				
51945	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	110	5	15	< 5	2.2	0.9	0.6	2.9	0.59	31.6				
51946	< 0.05	< 0.1	< 1	1.5	< 0.5	< 4	< 50	6	17	< 5	2.7	1.1	0.9	3.1	0.17	30.4				
51947	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	5	12	< 5	1.9	1.0	< 0.5	2.8	0.16	32.0				
51948	< 0.05	< 0.1	< 1	1.2	< 0.5	< 4	< 50	5	18	8	2.4	0.9	< 0.5	3.1	0.15	31.0				
51949	< 0.05	< 0.1	< 1	1.2	< 0.5	< 4	< 50	4	15	< 5	2.2	1.1	< 0.5	2.5	0.55	32.3				
51950	< 0.05	< 0.1	< 1	1.1	< 0.5	< 4	170	5	17	< 5	2.5	0.9	< 0.5	3.6	0.55	31.5				
51951	< 0.05	< 0.1	< 1	< 0.5	< 0.5	9	110	4	17	12	2.5	0.6	< 0.5	3.1	0.52	32.8				
51952	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	200	5	14	< 5	2.8	1.0	0.9	3.5	0.33	31.5				
51953	< 0.05	< 0.1	< 1	2.3	< 0.5	10	< 50	23	53	23	5.7	1.0	< 0.5	4.6	0.60	31.6				
51954	< 0.05	< 0.1	< 1	< 0.5	< 0.5	15	170	5	21	8	2.9	0.9	< 0.5	3.6	0.34	30.1				
51955	< 0.05	< 0.1	< 1	1.4	< 0.5	< 4	180	7	19	< 5	2.4	0.7	1.0	2.9	0.17	32.4				
51956	< 0.05	< 0.1	< 1	1.2	< 0.5	< 4	170	8	22	< 5	3.4	1.1	1.1	4.3	0.56	33.1				
51957	< 0.05	< 0.1	< 1	11.3	< 0.5	< 4	< 50	147	265	93	22.0	2.9	2.9	13.2	1.72	32.3	< 0.3	4.18	< 3	41
51958	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	4	16	< 5	1.8	0.8	< 0.5	1.9	0.41	31.8				
51959	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	3	8	< 5	1.4	0.6	< 0.5	2.2	0.06	32.1				
STAND. 51960 OREAS 50%	< 0.05	< 0.1	< 1	4.5	< 0.5	< 4	< 50	15	31	v	< 5	2.3	< 0.2	< 0.5	1.9	v	0.26	v	30.3	
51961	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	190	4	13	< 5	1.8	1.0	< 0.5	2.9	0.14	31.7				
51962	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	4	8	< 5	1.8	0.9	< 0.5	3.0	0.46	32.3				
51963	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	140	5	14	17	2.5	1.0	0.6	3.5	0.27	30.3				
51964	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	4	13	6	1.9	0.9	< 0.5	2.4	0.13	31.0				
51965	< 0.05	< 0.1	< 1	< 0.5	< 0.5	12	130	5	16	12	2.5	1.1	< 0.5	2.9	0.52	31.1				
51966	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	140	5	18	< 5	2.7	1.0	< 0.5	3.3	0.62	33.8				
51967	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	150	4	10	< 5	2.1	0.9	< 0.5	2.6	0.21	32.9				
51968	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	4	11	< 5	2.1	1.1	< 0.5	2.7	0.55	30.6				

Activation Laboratories Ltd.

Report: A10-5875 rev 1

4-acid digest

Analyte Symbol	Sn	Sr	Ta	Th	U	W	Zn	La	Ce	Nd	Sm	Eu	Tb	Yb	Lu	Mass	Ag	Al	As	Ba
Unit Symbol	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	g	ppm	%	ppm	ppm
Detection Limit	0.05	0.1	1	0.5	0.5	4	50	1	3	5	0.1	0.2	0.5	0.2	0.05		0.3	0.01	3	7
Analysis Method	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	TD-ICP	TD-ICP	TD-ICP	TD-ICP	
51969	< 0.05	< 0.1	< 1	1.5	< 0.5	< 4	100	5	< 3	< 5	2.4	1.0	< 0.5	3.2	0.54	32.6				
51970	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	3	10	< 5	1.7	0.9	< 0.5	2.4	0.43	30.3				
51971	< 0.05	< 0.1	< 1	< 0.5	< 0.5	8	100	4	12	< 5	1.7	0.9	< 0.5	3.0	0.08	31.0				
51972	< 0.05	< 0.1	< 1	0.6	< 0.5	10	150	5	13	< 5	2.4	0.8	< 0.5	3.3	0.54	31.3				
51973	< 0.05	< 0.1	< 1	< 0.5	2.5	11	140	5	15	16	2.5	1.0	< 0.5	3.7	0.54	32.4				
51974	< 0.05	< 0.1	< 1	< 0.5	2.5	18	< 50	4	13	< 5	1.8	0.9	< 0.5	2.7	0.51	30.5				
51975	< 0.05	< 0.1	< 1	< 0.5	< 0.5	31	160	4	10	13	2.1	0.5	< 0.5	3.0	0.48	31.3				
51976	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	140	5	23	< 5	2.6	1.0	0.9	3.5	0.54	32.5				
51977	< 0.05	< 0.1	< 1	< 0.5	< 0.5	21	< 50	10	26	15	4.2	1.2	1.1	4.4	0.70	33.2				
51978	< 0.05	< 0.1	< 1	< 0.5	< 0.5	28	< 50	6	23	< 5	2.8	1.2	< 0.5	3.6	0.66	31.2				
51979	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	170	5	18	19	2.4	0.4	< 0.5	3.7	0.17	31.2				
51980	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	170	9	24	< 5	3.5	1.1	< 0.5	4.2	0.57	31.2				
51981	< 0.05	< 0.1	< 1	0.9	< 0.5	< 4	< 50	5	14	< 5	2.2	1.2	< 0.5	2.8	0.53	32.1				
51982	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	3	10	< 5	1.5	0.9	< 0.5	1.9	0.32	30.6				
STAND. 51983 DRAES 13 & 13B	< 0.05	< 0.1	< 1	11.9	4.6	9	< 50 ⁴⁵	27	56	32	4.9	1.5	< 0.5	2.6	0.41	30.5				
51984	< 0.05	< 0.1	< 1	< 0.5	< 0.5	5	< 50	8	23	15	4.9	1.6	1.1	8.0	0.84	30.7	1.0	5.00	< 3	334
51985	< 0.05	< 0.1	< 1	< 0.5	< 0.5	5	210	5	14	< 5	2.5	1.1	< 0.5	3.2	0.28	31.8	0.4	5.92	< 3	191
51986	< 0.05	< 0.1	< 1	1.3	< 0.5	< 4	150	4	15	< 5	2.0	1.1	< 0.5	2.9	0.54	33.6				
51987	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	3	12	< 5	1.5	0.8	< 0.5	1.9	0.26	33.0				
51988	< 0.05	< 0.1	< 1	1.4	< 0.5	< 4	80	29	78	46	10.4	1.3	2.0	10.5	1.33	32.6				
51989	< 0.05	< 0.1	< 1	< 0.5	< 0.5	12	< 50	2	10	< 5	1.2	0.5	< 0.5	1.8	0.35	31.1				
51990	< 0.05	< 0.1	< 1	0.6	< 0.5	20	140	4	11	< 5	1.7	0.7	< 0.5	2.2	0.40	30.6				
51991	< 0.05	< 0.1	< 1	1.1	< 0.5	< 4	< 50	12	37	13	3.7	0.7	< 0.5	3.9	0.69	30.6				
51992	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	12	30	17	4.3	1.3	< 0.5	4.9	0.74	32.2				
51993	< 0.05	< 0.1	< 1	1.1	< 0.5	< 4	200	5	15	< 5	2.4	1.0	< 0.5	3.2	0.30	32.2				
51994	< 0.05	< 0.1	2	< 0.5	< 0.5	< 4	< 50	6	18	11	2.5	1.2	< 0.5	3.6	0.22	31.4				
51995	< 0.05	< 0.1	< 1	0.5	< 0.5	< 4	240	5	15	< 5	2.3	0.7	< 0.5	3.7	0.31	30.6				
51996	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	150	5	15	10	2.3	0.7	< 0.5	3.7	0.25	31.3				
51997	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	5	14	< 5	2.3	0.5	< 0.5	3.5	0.14	32.0				
51998	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	80	4	12	< 5	2.0	0.6	< 0.5	2.9	0.43	30.6				

Activation Laboratories Ltd.

Report: A10-5875 rev 1

NEAR TOTAL

Analyte Symbol	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	Sb	Si
Unit Symbol	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	
Detection Limit	1	2	0.01	0.3	1	1	1	0.01	1	1	0.01	0.01	1	1	0.01	0.001	3	5	0.01	
Analysis Method	TD-ICP																			
51909																				
51910																				
51911																				
51912																				
51913																				
51914																				
51915																				
51916																				
51917																				
51918																				
51919																				
51920																				
51921																				
51922																				
51923																				
51924																				
51925																				
51926																				
51927																				
51928																				
51929	<1	<2	1.22	0.6	81	16	3670	17.50	35	6	1.15	2.20	348	<1	0.72	38	0.020	<3	<5	1.47
51930																				
51931	<1	<2	3.50	0.8	64	24	284	17.60	20	<1	1.65	0.85	511	<1	2.04	25	0.012	<3	<5	13.40
51932																				
51933																				
51934																				
51935																				
51936	1	<2	5.40	0.5	32	22	20	27.90	10	2	0.05	1.99	986	<1	0.10	58	0.438	<3	<5	0.09
51937	<1	<2	3.27	1.9	22	8	<1	46.50	<1	<1	0.13	0.34	538	1	0.02	95	0.075	<3	<5	<0.01
51938	<1	<2	2.35	2.7	20	7	<1	53.50	<1	<1	0.08	0.24	428	<1	0.03	114	0.366	<3	8	<0.01

Activation Laboratories Ltd. Report: A10-5875 rev 1 NEAR TOTAL

Analyte Symbol	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	Sb	Si
Unit Symbol	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	%	ppm	ppm	%	
Detection Limit	1	2	0.01	0.3	1	1	1	0.01	1	1	0.01	0.01	1	1	0.01	1	3	5	0.01	
Analysis Method	TD-ICP																			
51939	<1	<2	5.75	0.8	44	27	25	17.40	22	<1	0.20	2.45	1240	<1	1.15	72	0.011	<3	<5	0.04
51940																				
51941																				
51942																				
51943																				
51944																				
51945																				
51946																				
51947																				
51948																				
51949																				
51950																				
51951																				
51952																				
51953																				
51954																				
51955																				
51956																				
51957	<1	<2	7.91	0.5	43	16	16	13.90	26	1	0.36	3.15	1090	<1	0.46	86	0.326	<3	<5	0.12
51958																				
51959																				
51960																				
51961																				
51962																				
51963																				
51964																				
51965																				
51966																				
51967																				
51968																				

Activation Laboratories Ltd.

Report: A10-5875 rev 1

NEAR TOTAL

Analyte Symbol	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	Sb	Si
Unit Symbol	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	
Detection Limit	1	2	0.01	0.3	1	1	1	0.01	1	1	0.01	0.01	1	1	0.01	1	3	5	0.01	
Analysis Method	TD-ICP																			
51969																				
51970																				
51971																				
51972																				
51973																				
51974																				
51975																				
51976																				
51977																				
51978																				
51979																				
51980																				
51981																				
51982																				
51983																				
51984	< 1	< 2	6.77	0.4	43	90	1190	10.20	22	< 1	1.67	2.97	1440	< 1	0.15	73	0.043	< 3	< 5	0.34
51985	< 1	< 2	7.10	< 0.3	45	69	641	9.47	24	< 1	0.79	2.54	1440	< 1	1.48	74	0.035	< 3	< 5	0.17
51986																				
51987																				
51988																				
51989																				
51990																				
51991																				
51992																				
51993																				
51994																				
51995																				
51996																				
51997																				
51998																				

Activation Laboratories Ltd.

Report: A10-5875 rev 1

FUSION

Analyte Symbol	Sc	Sr	Te	Tl	Tl	U	V	W	Y	Zn	Zr	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃ (T)	MnO	MgO	CaO	Na ₂ O	K ₂ O	TiO ₂
Unit Symbol	ppm	ppm	ppm	%	ppm	%	%	%	%	%	%	%	%	%						
Detection Limit	4	1	2	0.01	5	10	2	5	1	1	5	0.01	0.01	0.01	0.001	0.01	0.01	0.01	0.01	0.001
Analysis Method	TD-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP										
51909																				
51910																				
51911																				
51912																				
51913																				
51914																				
51915																				
51916																				
51917																				
51918																				
51919																				
51920																				
51921																				
51922																				
51923																				
51924																				
51925																				
51926																				
51927																				
51928																				
51929	4	22	< 2	0.25	< 5	< 10	320	19	20	177	1100									
51930																				
51931	5	45	< 2	0.24	< 5	< 10	269	22	19	21	656									
51932																				
51933																				
51934																				
51935																				
51936	22	43	17	0.36	< 5	< 10	328	10	67	57	101									
51937	< 4	28	14	0.20	< 5	< 10	349	6	12	46	20	8.04	1.63	79.28	0.110	0.71	5.56	0.04	0.18	0.427
51938	4	23	8	0.36	< 5	< 10	638	8	54	48	24	4.53	1.22	88.35	0.094	0.49	3.83	0.05	0.10	0.838

Activation Laboratories Ltd.

Report: A10-5875 rev 1

FUSION

Analyte Symbol	Sc	Sr	Ts	Ti	Tl	U	V	W	Y	Zn	Zr	SiO2	Al2O3	Fe2O3(T)	MnO	MgO	CaO	Na2O	K2O	TiO2
Unit Symbol	ppm	ppm	ppm	%	ppm	%	%	%	%	%	%	%	%							
Detection Limit	4	1	2	0.01	5	10	2	5	1	1	5	0.01	0.01	0.01	0.001	0.01	0.01	0.01	0.001	
Analysis Method	TD-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP											
51939	32	58	< 2	0.20	< 5	< 10	436	11	6	83	47									
51940																				
51941																				
51942																				
51943																				
51944																				
51945																				
51946																				
51947																				
51948																				
51949																				
51950																				
51951																				
51952																				
51953																				
51954																				
51955																				
51956																				
51957	25	69	11	0.48	< 5	< 10	389	< 5	53	66	34									
51958																				
51959																				
51960																				
51961																				
51962																				
51963																				
51964																				
51965																				
51966																				
51967																				
51968																				

Activation Laboratories Ltd.

Report: A10-5875 rev 1

FUSION

Analyte Symbol	Sc	Sr	Te	Tl	U	V	W	Y	Zn	Zr	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃ (T)	MnO	MgO	CaO	Na ₂ O	K ₂ O	TiO ₂
Unit Symbol	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	%	%	%	%	%	%	%	%	
Detection Limit	4	1	2	0.01	5	10	2	5	1	1	0.01	0.01	0.01	0.001	0.01	0.01	0.01	0.001	
Analysis Method	TD-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP										
51969																			
51970																			
51971																			
51972																			
51973																			
51974																			
51975																			
51976																			
51977																			
51978																			
51979																			
51980																			
51981																			
51982																			
51983																			
51984	37	42	< 2	0.28	< 5	< 10	219	< 5	11	95	27								
51985	36	113	< 2	0.29	< 5	< 10	206	< 5	13	85	31								
51986																			
51987																			
51988																			
51989																			
51990																			
51991																			
51992																			
51993																			
51994																			
51995																			
51996																			
51997																			
51998																			

Activation Laboratories Ltd. Report: A10-5875 rev 1

Analyte Symbol	P2O5	LOI	Total	Sc	Be	V	Ba	Sr	Y	Zr	Cr	Co	Ni	Cu	Zn	Ga	Ge	As	Rb	Nb
Unit Symbol	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm						
Detection Limit	0.01		0.01	1	1	5	3	2	2	4	20	1	20	10	30	1	1	5	2	1
Analysis Method	FUS-ICP	FUS-MS																		
51909																				
51910																				
51911	0.21	6.80	98.75	49	< 1	809	13	50	34	135	< 20	68	60	90	220	20	1	7	< 2	9
51912																				
51913																				
51914																				
51915																				
51916																				
51917																				
51918																				
51919																				
51920																				
51921																				
51922																				
51923																				
51924																				
51925																				
51926																				
51927																				
51928																				
51929																				
51930																				
51931																				
51932																				
51933																				
51934																				
51935																				
51936																				
51937	0.24	2.22	98.43	7	< 1	435	45	33	23	21	< 20	31	100	< 10	40	31	3	< 5	5	3
51938	1.11	-0.50	100.10	6	1	771	15	26	67	10	< 20	34	120	< 10	50	35	3	< 5	< 2	3

Activation Laboratories Ltd. Report: A10-5875 rev 1

Analyte Symbol	Mo	Ag	In	Sn	Sb	Cs	La	Ce	Pr	Nd	Sm	Eu	Gd	Tb	Dy	Ho	Er	Tm	Yb	Lu
Unit Symbol	ppm																			
Detection Limit	2	0.5	0.2	1	0.5	0.5	0.1	0.1	0.05	0.1	0.1	0.05	0.1	0.1	0.1	0.1	0.1	0.05	0.1	0.04
Analysis Method	FUS-MS																			
51909																				
51910																				
51911	<2	<0.5	<0.2	1	<0.5	<0.5	6.8	18.5	2.73	13.4	4.0	1.20	4.9	0.9	5.8	1.2	3.6	0.55	3.8	0.61
51912																				
51913																				
51914																				
51915																				
51916																				
51917																				
51918																				
51919																				
51920																				
51921																				
51922																				
51923																				
51924																				
51925																				
51926																				
51927																				
51928																				
51929																				
51930																				
51931																				
51932																				
51933																				
51934																				
51935																				
51936																				
51937	<2	<0.5	<0.2	8	<0.5	<0.5	13.2	31.2	3.92	16.7	3.7	0.52	3.9	0.6	3.5	0.7	2.0	0.28	1.7	0.23
51938	<2	<0.5	<0.2	9	<0.5	<0.5	59.1	141.0	18.00	74.7	15.6	1.55	16.5	2.6	14.3	2.8	7.7	1.03	5.8	0.79

Activation Laboratories Ltd. Report: A10-5875 rev 1

Analyte Symbol	Hf	Ta	W	Tl	Pb	Bi	Th	U
Unit Symbol	ppm							
Detection Limit	0.2	0.1	1	0.1	5	0.4	0.1	0.1
Analysis Method	FUS-MS							
51909								
51910								
51911	3.4	0.5	< 1	< 0.1	< 5	< 0.4	1.2	0.2
51912								
51913								
51914								
51915								
51916								
51917								
51918								
51919								
51920								
51921								
51922								
51923								
51924								
51925								
51926								
51927								
51928								
51929								
51930								
51931								
51932								
51933								
51934								
51935								
51936								
51937	0.4	0.1	< 1	< 0.1	< 5	< 0.4	2.0	0.2
51938	0.3	< 0.1	< 1	< 0.1	< 5	< 0.4	2.0	0.5

Activation Laboratories Ltd. Report: A10-5875 rev 1

17

Activation Laboratories Ltd. Report: A10-5875 rev 1

Activation Laboratories Ltd. Report: A10-5875 rev 1

Quality Control

Analyte Symbol	Sc	Sr	Te	Ti	Tl	U	V	W	Y	Zn	Zr	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃ (T)	MnO	MgO	CaO	Na ₂ O	K ₂ O
Unit Symbol	ppm	ppm	ppm	%	ppm	%	%	%	%	%	%	%							
Detection Limit	4	1	2	0.01	5	10	2	5	1	1	5	0.01	0.01	0.01	0.001	0.01	0.01	0.01	
Analysis Method	TD-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP	FUS-ICP										
DMMAS 111 Cert																			
DMMAS 111 Meas																			
DMMAS 111 Cert																			
51938 Orig																			
51938 Split																			
51938 Orig												4.50	1.13	87.940	0.0930	0.480	3.820	0.050	0.100
51938 Dup												4.57	1.31	88.770	0.0940	0.490	3.840	0.050	0.100
51958 Orig																			
51958 Split																			
51968 Orig																			
51968 Split																			
51998 Orig																			
51998 Split																			
Method Blank	< 4	< 1	< 2	< 0.01	< 5	< 10	< 2	< 5	< 1	< 1	< 5								
Method Blank	< 4	< 1	< 2	< 0.01	< 5	< 10	< 2	< 5	< 1	< 1	< 5								
Method Blank	< 4	< 1	< 2	< 0.01	< 5	< 10	< 2	< 5	< 1	< 1	< 5								
Method Blank	< 4	< 1	< 2	< 0.01	< 5	< 10	< 2	< 5	< 1	< 1	< 5								
Method Blank	< 4	< 1	< 2	< 0.01	< 5	< 10	< 2	< 5	< 1	< 1	< 5								
Method Blank	< 4	< 1	< 2	< 0.01	< 5	< 10	< 2	< 5	< 1	< 1	< 5								
Method Blank	< 4	< 1	< 2	< 0.01	< 5	< 10	< 2	< 5	< 1	< 1	< 5								
Method Blank	< 4	< 1	< 2	< 0.01	< 5	< 10	< 2	< 5	< 1	< 1	< 5								
Method Blank	< 4	< 1	< 2	< 0.01	< 5	< 10	< 2	< 5	< 1	< 1	< 5								
Method Blank	< 4	< 1	< 2	< 0.01	< 5	< 10	< 2	< 5	< 1	< 1	< 5								
Method Blank	< 4	< 1	< 2	< 0.01	< 5	< 10	< 2	< 5	< 1	< 1	< 5								
Method Blank	< 4	< 1	< 2	< 0.01	< 5	< 10	< 2	< 5	< 1	< 1	< 5								
Method Blank	< 4	< 1	< 2	< 0.01	< 5	< 10	< 2	< 5	< 1	< 1	< 5								
Method Blank	< 4	< 1	< 2	< 0.01	< 5	< 10	< 2	< 5	< 1	< 1	< 5								
Method Blank	< 4	< 1	< 2	< 0.01	< 5	< 10	< 2	< 5	< 1	< 1	< 5								
Method Blank	< 4	< 1	< 2	< 0.01	< 5	< 10	< 2	< 5	< 1	< 1	< 5								
Method Blank	< 4	< 1	< 2	< 0.01	< 5	< 10	< 2	< 5	< 1	< 1	< 5								
Method Blank	< 4	< 1	< 2	< 0.01	< 5	< 10	< 2	< 5	< 1	< 1	< 5								
Method Blank	< 4	< 1	< 2	< 0.01	< 5	< 10	< 2	< 5	< 1	< 1	< 5								

Activation Laboratories Ltd. Report: A10-5875 rev 1

Quality Control		P2O5	Sc	Be	V	Ba	Sr	Y	Zr	LOI	Total	Cr	Co	Ni	Cu	Zn	Ga	Ge	As	Rb
Unit Symbol		%	ppm	%	%	ppm														
Detection Limit		0.01	1	1	5	3	2	2	4		0.01	20	1	20	10	30	1	1	5	2
Analysis Method	FUS-ICP	FUS-MS																		

DMMAS 111
Cert

DMMAS 111

Meas

DMMAS 111
Cert

51938 Orig

51938 Split

51938 Orig	1.1000	6.00	1.00	768.00	15	25.0	66.0	10.0	-0.50	99.56	< 20	34.00	120.00	< 10	50.000	35.0	3.00	< 5	2.00
51938 Dup	1.1200	6.00	1.00	773.00	15	26.0	67.0	9.0	-0.50	100.70	< 20	33.00	120.00	< 10	40.000	35.0	2.00	< 5	< 2

51958 Orig

51958 Split

51968 Orig

51968 Split

51998 Orig

51998 Split

Method

Blank

Method Blank

< 20	< 1	< 20	< 10	< 30	< 1	< 1	< 5	< 2
------	-----	------	------	------	-----	-----	-----	-----

20

Activation Laboratories Ltd. Report: A10-5875 rev 1

Quality Control

Analyte Symbol	Hf	Ta	W	Tl	Pb	Bi	Th	U
Unit Symbol	ppm							
Detection Limit	0.2	0.1	1	0.1	5	0.4	0.1	0.1
Analysis Method	FUS-MS							

DMMAS 111

Cert

DMMAS 111

Meas

DMMAS 111

Cert

51938 Orig

51938 Split

51938 Orig

0.30	< 0.1	< 1	< 0.1	< 5	< 0.4	2.00	0.500
0.30	< 0.1	< 1	< 0.1	< 5	< 0.4	2.00	0.500

51958 Orig

51958 Split

51968 Orig

51968 Split

51998 Orig

51998 Split

Method

Blank

Method Blank

< 0.2	< 0.1	< 1	< 0.1	< 5	< 0.4	< 0.1	< 0.1
-------	-------	-----	-------	-----	-------	-------	-------



ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: 604 984 0221 Fax: 604 984 0218 www.alsglobal.com

To: CLAIM POST RESOURCES INC.
141 ADELAIDE STREET WEST
SUITE 903
TORONTO ON M5H 3L5

Page: 1
Finalized Date: 25-OCT-2010
Account: CLAPST

CERTIFICATE TM10149319

Project: CP12D- DAXL

P.O. No.:

This report is for 67 ~~Crushed Rock~~ samples submitted to our lab in Timmins, ON, Canada on 14-OCT-2010.

The following have access to data associated with this certificate:

HERMANN DAXL

15 CORE
49 CRUSHED CORE
3 PULP STANDARDS

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
LOG-24	Pulp Login - Rcd w/o Barcode
CRU-21	Crush entire sample > 70% - 6 mm
PUL-31	TOTAL - Pulverize split to 85% < 75 um
PUL-32	TOTAL - Pulverize 1000g to 85% < 75 um

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
PGM-ICP23	Pt, Pd, Au 30g FA ICP ✓	ICP- AES

To: CLAIM POST RESOURCES INC.
ATTN: HERMANN DAXL
141 ADELAIDE STREET WEST
SUITE 903
TORONTO ON M5H 3L5

CP-10-12

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature:

Colin Ramshaw, Vancouver Laboratory Manager



ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: 604 984 0221 Fax: 604 984 0218 www.alsglobal.com

To: CLAIM POST RESOURCES INC.
141 ADELAIDE STREET WEST
SUITE 903
TORONTO ON M5H 3L5

Page: 2 - A
Total # Pages: 3 (A)
Finalized Date: 25-OCT-2010
Account: CLAPST

Pulverized totals received -
- 30 g Fire Assays ICP-AES

Project: CP12D-DAXL

CERTIFICATE OF ANALYSIS TM10149319

Sample Description	Method Analyte Units LOR	WEI-21 Revd Wt. kg	PGM-ICP23 Au ppm	PGM-ICP23 Pt ppm	PGM-ICP23 Pd ppm
51911		0.70	<0.001	<0.005	0.001
51912		0.16	0.067	<0.005	<0.001
~51919 OREAS H3 Standard		0.93	1.940	0.005	0.001
51920		0.63	0.008	<0.005	0.001
51921		0.57	0.005	<0.005	0.001
51922		0.22	<0.001	<0.005	0.001
51923		0.47	<0.001	<0.005	0.001
51924		0.23	0.056	<0.005	0.001
51925		0.25	0.006	<0.005	0.001
51926		0.70	0.005	<0.005	0.001
51927		0.29	0.022	<0.005	0.001
51929		0.70	0.312	<0.005	0.001
51930		0.39	0.005	<0.005	0.001
51932		0.59	0.002	<0.005	<0.001
51936 much mt-il		0.62	0.002	<0.005	<0.001
51937 very much mt-il		0.73	<0.001	<0.005	<0.001
51940		0.27	0.001	<0.005	0.001
51941		0.28	0.072	<0.005	0.001
51943		0.64	0.033	<0.005	0.001
51944		0.68	0.044	<0.005	0.001
51946		0.28	0.090	<0.005	0.001
51951		0.28	0.096	<0.005	0.002
51955		0.64	0.025	<0.005	0.001
51958		0.27	0.012	<0.005	0.001
51959		0.38	0.074	<0.005	<0.001
51961		0.53	0.003	<0.005	0.001
51962		0.28	0.140	<0.005	0.001
51964		0.51	0.115	<0.005	0.001
51965		0.62	0.229	<0.005	0.001
51966		0.84	0.007	<0.005	0.001
51967		0.71	0.010	<0.005	0.001
51968		0.81	0.004	<0.005	0.001
51969		0.50	0.009	<0.005	0.001
51970		0.27	0.143	<0.005	0.001
51971		0.76	0.022	<0.005	0.001
51972		0.66	0.011	<0.005	0.001
51973		0.57	0.140	<0.005	0.001
51974		0.88	0.224	<0.005	0.001
51975		0.86	0.349	<0.005	0.001
51977		0.65	0.236	<0.005	0.001



ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: 604 984 0221 Fax: 604 984 0218 www.alsglobal.com

To: CLAIM POST RESOURCES INC.
141 ADELAIDE STREET WEST
SUITE 903
TORONTO ON M5H 3L5

Page: 3 - A
Total # Pages: 3 (A)
Finalized Date: 25- OCT- 2010
Account: CLAPST

Pulverized totals received -
- 30 g Fire Assays ICP-AES

Project: CP12D-DAXL

CERTIFICATE OF ANALYSIS TM10149319

Sample Description	Method Analyte Units LOR	WEI- 21 Recvd Wt.	PGM-ICP23 Au	PGM-ICP23 Pt	PGM-ICP23 Pd
		kg	ppm	ppm	ppm
51978		0.51	0.005	<0.005	<0.001
51980		0.79	0.022	<0.005	0.001
51983 OREAS 13b Standard		0.05	0.209	0.499	0.429
51984		0.15	0.020	<0.005	0.001
51988		0.58	0.002	<0.005	0.001
51989		0.36	0.119	<0.005	<0.001
51990		0.87	0.010	<0.005	0.001
51992		0.81	0.004	<0.005	0.001
51993		0.72	0.011	<0.005	0.001
51994		0.30	0.239	<0.005	0.001
51995		0.56	0.004	<0.005	0.001
57380		0.71	0.118	<0.005	0.001
57381		0.52	0.561	<0.005	0.001
57382		0.54	0.021	<0.005	0.001
57383		0.58	0.030	<0.005	0.001
57384		0.64	0.007	<0.005	<0.001
57385		0.76	0.004	<0.005	0.001
57386		0.76	0.006	<0.005	0.001
57387		0.58	0.007	<0.005	0.001
57388		0.42	0.036	<0.005	<0.001
57389		0.54	0.005	<0.005	0.001
57390		0.59	0.003	<0.005	0.001
57391		0.59	0.301	<0.005	<0.001
57392		0.65	0.022	<0.005	<0.001
57393		0.81	0.001	<0.005	<0.001
57394 DAX1 Test ✓		0.66	0.009	<0.005	<0.001
		0.05	0.332	0.087	0.282
519.. Series is fine rejects from ACTLABS]					
573.. Series is additional core } ALL OF CP-10-12					
Note: No sparse-particle effect was found for gold, and there was no Pt-Pd.					

TM10149319 - Finalized

CLIENT : CLAPST - Claim Post Resources Inc.

of SAMPLES : 67

DATE RECEIVED : 2010-10-14

PROJECT : CP12D-DAXL

CERTIFICATE COMMENTS :

PO NUMBER :

PGM-ICP23 PGM-ICP23 PGM-ICP23

SAMPLE	Au	Pt	Pd
DESCRIPTION	ppm	ppm	ppm
OREAS-45c	0.046	0.067	0.047
PD1	0.512	0.46	0.541
PD1	0.522	0.441	0.546
OREAS-45c	0.05	0.069	0.049
OREAS-45c	0.046	0.061	0.046
PD1	0.535	0.465	0.559
PGMS-17	0.94	1.04	4.31
OXD73	0.404	-0.005	0.001
PGMS-17	0.882	1.015	4.24
OXD73	0.42	-0.005	-0.001
PGMS-17	0.876	0.988	4.21
OXD73	0.399	-0.005	-0.001
BLANK	-0.001	-0.005	-0.001
BLANK	-0.001	-0.005	-0.001
BLANK	-0.001	-0.005	-0.001

✓

TM10149319 - Finalized

CLIENT : CLAPST - Claim Post Resources Inc.

of SAMPLES : 67

DATE RECEIVED : 2010-10-14

PROJECT : CP12D-DAXL

CERTIFICATE COMMENTS :

PO NUMBER :

PGM-ICP23 PGM-ICP23 PGM-ICP23

SAMPLE	Au	Pt	Pd
DESCRIPTION	ppm	ppm	ppm
51937	-0.001	-0.005	-0.001
51937	0.002	-0.005	0.001
51972	0.011	-0.005	0.001
51972	0.005	-0.005	0.001

✓

Quality Analysis ...



Innovative Technologies

Date Submitted: 21-Sep-10
Invoice No.: A10-6253 (i)
Invoice Date: 01-Nov-10
Your Reference: CP-13-15-DAXL

CLAIM POST RESOURCES INC
39-630 RIVERPARK ROAD
TIMMINS ON P4P 1B4
Canada

ATTN: Herman Daxl

CERTIFICATE OF ANALYSIS

78 CORE HALVES NQ
3 PULP STANDARDS

82 Rock samples were submitted for analysis. **ALL PULVERIZED ENTIRELY.**

The following analytical package was requested Code ID INAA(INAAGEO) NEUTRON ACTIVATION ~30g

REPORT **A10-6253 (I)**

This report may be reproduced without our consent. If only selected portions of the report are reproduced, permission must be obtained. If no instructions were given at time of sample submittal regarding excess material, it will be discarded within 90 days of this report. Our liability is limited solely to the analytical cost of these analyses. Test results are representative only of material submitted for analysis.

Notes:

For values exceeding the upper limits we recommend assays.

CERTIFIED BY :

A handwritten signature in black ink, appearing to read "Emmanuel Eseme".

Emmanuel Eseme , Ph.D.

Quality Control

ACTIVATION LABORATORIES LTD.

All pulverized entirely

Activation Laboratories Ltd.

Report: A10-6253 (I) rev 1

Neutron Activation ~ 30 g

Analyte Symbol	Au	Ag	As	Ba	Br	Ca	Co	Cr	Cs	Fe	Hf	Hg	Ir	Mo	Na	Ni	Rb	Sb	Sc	Se
Unit Symbol	ppb	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	%	ppm	ppm	ppm	ppm	
Detection Limit	5	5	2	100	1	1	5	10	2	0.02	1	1	5	5	0.05	50	30	0.2	0.1	
Analysis Method	INAA	INAA	INAA	INAA	INAA															
57251 BLANK	<5	<5	<2	500	<1	6	13	30	<2	3.17	<1	<1	<5	<5	1.44	<50	70	<0.2	8.8	<5
57252	<5	<5	<2	500	<1	5	18	30	<2	4.62	3	<1	<5	<5	2.98	<50	<30	<0.2	15.7	<5
57253	<5	<5	<2	400	<1	6	7	<10	<2	3.24	7	<1	5	<5	0.08	<50	<30	<0.2	4.5	<5
57254	<5	<5	3	<100	3	4	8	10	<2	2.75	4	<1	<5	<5	1.29	<50	50	<0.2	5.9	<5
57255	<5	<5	<2	<100	3	7	26	<10	<2	7.22	2	<1	<5	<5	1.51	<50	<30	<0.2	27.5	<5
57256	<5	<5	6	<100	<1	4	37	<10	<2	9.18	3	<1	<5	<5	2.03	<50	<30	<0.2	28.7	<5
57257	<5	<5	3	<100	<1	5	31	<10	<2	8.14	2	<1	<5	<5	1.88	<50	<30	<0.2	26.5	<5
57258 STANDARD ✓ 186	<5	45	700	<1	3	63	8290	5	6.43	2	<1	34	<5	1.38	1450	90	1.6	20.1	<5	
57259	<5	<5	<2	<100	<1	4	27	<10	<2	7.22	2	<1	<5	<5	2.17	<50	<30	<0.2	22.8	<5
57260	<5	<5	<2	<100	<1	<1	37	<10	<2	8.31	<1	<1	<5	<5	1.68	<50	<30	<0.2	27.0	<5
57261	<5	<5	<2	<100	<1	9	36	<10	<2	8.59	<1	<1	<5	<5	0.71	<50	<30	<0.2	24.4	<5
57262	<5	<5	<2	<100	<1	5	30	20	<2	8.76	6	<1	<5	<5	0.94	<50	<30	<0.2	28.0	<5
57263	<5	<5	<2	<100	<1	6	49	<10	<2	9.44	2	<1	<5	<5	1.76	<50	<30	<0.2	30.9	<5
57264	10	<5	<2	200	<1	3	34	<10	<2	6.79	3	<1	<5	<5	1.37	<50	<30	<0.2	24.4	<5
57265	<5	<5	<2	<100	<1	4	24	200	<2	4.62	3	<1	<5	<5	1.58	<50	<30	<0.2	17.7	<5
57266	<5	<5	3	200	3	8	26	170	<2	5.66	<1	<1	<5	<5	0.62	<50	40	<0.2	16.6	<5
57267	<5	<5	3	<100	<1	<1	6	20	<2	2.22	5	<1	<5	<5	3.36	<50	<30	<0.2	6.7	<5
57268	51	<5	10	<100	<1	3	43	<10	<2	5.34	4	<1	<5	<5	1.47	200	<30	<0.2	19.5	<5
57269	<5	<5	5	<100	4	<1	7	20	<2	2.05	4	<1	<5	<5	3.24	<50	<30	<0.2	6.2	<5
57270	39	<5	8	<100	<1	7	32	<10	<2	7.43	3	<1	<5	<5	1.21	<50	<30	<0.2	29.9	<5
57271	10	<5	6	<100	<1	5	37	<10	<2	9.44	2	<1	<5	<5	1.26	<50	<30	<0.2	29.8	<5
57272	<5	<5	5	<100	<1	5	27	<10	<2	6.82	<1	<1	<5	<5	0.36	<50	<30	<0.2	15.7	<5
57273	<5	<5	6	400	<1	7	31	<10	<2	7.11	2	<1	<5	<5	0.43	<50	<30	0.4	29.6	<5
57274	<5	<5	5	<100	3	7	28	<10	3	8.64	3	<1	<5	<5	0.91	250	<30	0.6	26.8	<5
57275	<5	<5	5	<100	2	6	37	<10	<2	9.45	2	<1	<5	<5	1.37	<50	<30	0.5	28.8	<5
57276	<5	<5	5	<100	<1	5	27	<10	<2	8.05	<1	<1	<5	<5	0.05	<50	<30	0.8	22.0	5
57277	385	<5	4	<100	<1	4	16	<10	<2	6.94	<1	<1	<5	<5	<0.05	<50	<30	0.4	14.0	<5
57278	247	<5	7	400	<1	3	25	10	<2	6.61	<1	<1	<5	<5	<0.05	<50	<30	0.7	18.0	<5
57279	134	<5	10	300	<1	2	17	<10	<2	3.91	<1	<1	<5	<5	<0.05	<50	<30	2.4	10.4	<5
57280	<5	<5	12	<100	<1	2	34	<10	<2	8.17	2	<1	<5	<5	<0.05	<50	<30	0.8	25.4	<5

Activation Laboratories Ltd. Report: A10-6253 (I) rev 1

Analyte Symbol	Sn	Sr	Ta	Th	U	W	Zn	La	Ce	Nd	Sm	Eu	Tb	Yb	Lu	Mass
Unit Symbol	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	g
Detection Limit	0.05	0.1	1	0.5	0.5	4	50	1	3	5	0.1	0.2	0.5	0.2	0.05	
Analysis Method	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA
57258-BLANK	<0.05	<0.1	<1	0.8	<0.5	<4	<50	3	9	<5	1.1	0.9	<0.5	1.3	<0.14	33.1
57252	<0.05	<0.1	<1	<0.5	<0.5	<4	<50	3	<3	<5	1.5	1.0	<0.5	2.1	0.40	36.7
57253	<0.05	<0.1	<1	4.2	1.6	<4	<50	17	42	16	4.9	1.1	0.7	4.8	0.86	28.8
57254	<0.05	<0.1	<1	3.7	<0.5	<4	<50	19	48	22	4.2	1.2	<0.5	2.5	0.36	30.3
57255	<0.05	<0.1	<1	1.4	<0.5	7	<50	7	18	<5	2.9	1.6	<0.5	3.5	0.09	34.3
57256	<0.05	<0.1	<1	<0.5	<0.5	<4	220	7	22	15	3.0	1.7	<0.5	3.4	0.20	35.7
57257	<0.05	<0.1	<1	<0.5	2.2	<4	170	7	20	18	2.5	1.5	<0.5	3.0	<0.05	37.5
57258-STAND.	<0.05	<0.1	<1	8.5	<0.5	<4	170	20	46	15	4.0	1.4	<0.5	1.9	<0.18	29.8
57259	<0.05	<0.1	<1	<0.5	<0.5	<4	<50	6	20	16	3.0	1.9	<0.5	4.3	0.43	34.8
57260	<0.05	<0.1	<1	<0.5	<0.5	<4	<50	6	10	<5	2.5	1.6	0.9	3.3	0.21	32.3
57261	<0.05	<0.1	<1	<0.5	<0.5	<4	<50	6	19	17	2.6	1.0	<0.5	3.0	<0.05	32.9
57262	<0.05	<0.1	<1	1.3	1.8	<4	160	12	31	19	5.0	1.7	<0.5	6.5	0.73	32.6
57263	<0.05	<0.1	<1	1.1	<0.5	<4	140	6	15	<5	2.3	1.3	0.7	3.2	0.20	36.9
57264	<0.05	<0.1	<1	<0.5	<0.5	51	150	5	14	<5	2.0	1.3	<0.5	2.5	0.10	35.2
57265	<0.05	<0.1	<1	2.0	<0.5	<4	160	13	29	12	3.1	1.4	<0.5	2.4	0.08	33.6
57266	<0.05	<0.1	<1	1.6	<0.5	<4	120	16	40	14	3.6	1.6	<0.5	1.8	0.31	33.7
57267	<0.05	<0.1	<1	5.5	2.6	<4	<50	12	34	10	4.6	1.2	0.9	6.0	0.88	31.3
57268	<0.05	<0.1	<1	2.5	<0.5	<4	150	21	45	25	5.2	1.8	0.7	5.1	0.68	34.3
57269	<0.05	<0.1	<1	4.0	<0.5	<4	<50	24	53	20	4.1	1.2	<0.5	4.3	0.72	31.3
57270	<0.05	<0.1	<1	<0.5	<0.5	<4	1980	8	20	<5	3.1	1.5	<0.5	3.6	0.63	34.5
57271	<0.05	<0.1	<1	<0.5	<0.5	<4	100	11	32	24	5.4	2.2	1.3	5.1	0.82	35.6
57272	<0.05	<0.1	<1	<0.5	<0.5	<4	130	6	21	10	2.8	1.0	0.8	2.5	0.50	33.8
57273	<0.05	<0.1	<1	1.1	<0.5	<4	150	11	27	18	5.5	2.1	<0.5	5.3	0.31	34.9
57274	<0.05	<0.1	<1	<0.5	<0.5	<4	150	9	25	<5	4.6	1.8	<0.5	4.0	0.31	32.2
57275	<0.05	<0.1	<1	<0.5	<0.5	<4	100	11	30	15	5.2	2.2	0.7	4.5	0.38	34.8
57276	<0.05	<0.1	<1	0.8	<0.5	<4	690	9	26	14	4.4	1.8	<0.5	4.1	0.30	31.5
57277	<0.05	<0.1	<1	<0.5	<0.5	<4	1270	6	20	<5	2.9	1.0	<0.5	2.5	0.42	35.2
57278	<0.05	<0.1	<1	<0.5	<0.5	<4	6400	8	23	15	3.7	1.4	<0.5	3.2	0.52	31.8
57279	<0.05	<0.1	<1	<0.5	<0.5	<4	14900	5	13	9	2.1	0.7	<0.5	1.7	0.11	31.1
57280	<0.05	<0.1	<1	<0.5	<0.5	<4	570	12	36	21	5.3	1.6	1.0	4.6	0.42	32.5

All pulverized entirely

Activation Laboratories Ltd.

Report: A10-6253 (I) rev 1

Neutron Activation ~ 30 g

Analyte Symbol	Au	Ag	As	Ba	Br	Ca	Co	Cr	Cs	Fe	Hf	Hg	Ir	Mo	Na	Ni	Rb	Sb	Sc	Se
Unit Symbol	ppb	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	%	ppm	ppm	ppm	ppm	
Detection Limit	5	5	2	100	1	1	5	10	2	0.02	1	1	5	5	0.05	50	30	0.2	0.1	5
Analysis Method	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	
57281	12	< 5	< 2	300	< 1	5	22	< 10	< 2	7.41	3	< 1	< 5	< 5	< 0.05	< 50	< 30	0.7	20.3	< 5
57282	< 5	< 5	< 2	500	< 1	< 1	6	< 10	< 2	2.75	6	< 1	< 5	< 5	0.07	< 50	70	0.3	7.5	< 5
57283	< 5	< 5	< 2	< 100	< 1	5	34	< 10	< 2	9.27	2	< 1	< 5	< 5	1.20	< 50	< 30	< 0.2	24.0	< 5
57284 STANDARD 1860	< 5	8	200	3	< 1	17	140	< 2	4.07	2	< 1	< 5	27	0.15	< 50	< 30	13.0	9.8	13	
57285	11	< 5	3	< 100	< 1	5	29	< 10	< 2	9.01	3	< 1	< 5	< 5	1.28	< 50	50	0.5	29.0	< 5
57286	< 5	< 5	< 2	200	< 1	13	28	< 10	< 2	9.01	3	< 1	< 5	< 5	0.63	< 50	< 30	< 0.2	21.8	< 5
57287	< 5	< 5	3	< 100	< 1	4	30	10	< 2	8.49	2	< 1	< 5	< 5	0.86	< 50	< 30	< 0.2	24.1	< 5
57288	30	< 5	< 2	< 100	< 1	11	13	10	< 2	6.12	< 1	< 1	< 5	< 5	0.13	< 50	< 30	< 0.2	13.4	< 5
57289	< 5	< 5	< 2	400	< 1	< 1	< 5	< 10	< 2	2.47	13	< 1	< 5	< 5	1.90	< 50	< 30	0.3	5.0	< 5
57290	31	< 5	< 2	400	< 1	< 1	7	< 10	< 2	2.24	8	< 1	< 5	< 5	2.75	< 50	< 30	< 0.2	7.5	< 5
57291	< 5	< 5	< 2	< 100	< 1	6	30	240	< 2	4.75	3	< 1	< 5	< 5	0.73	< 50	< 30	< 0.2	14.2	< 5
57292	7	< 5	< 2	< 100	< 1	14	15	< 10	< 2	5.40	2	< 1	< 5	< 5	0.61	< 50	< 30	< 0.2	12.2	< 5
57293	< 5	< 5	< 2	< 100	< 1	4	32	< 10	< 2	9.60	3	< 1	< 5	< 5	1.37	< 50	< 30	0.6	28.6	< 5
57294	< 5	< 5	< 2	300	< 1	7	22	10	< 2	6.53	2	< 1	< 5	< 5	0.28	< 50	< 30	< 0.2	23.4	< 5
57295	< 5	< 5	3	< 100	< 1	5	37	< 10	< 2	9.09	4	< 1	< 5	< 5	2.65	< 50	< 30	0.4	23.0	< 5
57296	< 5	< 5	< 2	500	< 1	< 1	11	< 10	< 2	8.36	13	< 1	< 5	< 5	2.20	< 50	60	< 0.2	27.0	< 5
57297	< 5	< 5	14	400	< 1	< 1	29	< 10	< 2	9.36	13	< 1	< 5	< 5	1.39	< 50	60	< 0.2	25.8	< 5
57298	< 5	< 5	4	< 100	< 1	< 1	25	10	< 2	6.72	11	< 1	< 5	< 5	2.46	< 50	< 30	< 0.2	13.9	< 5
57299	< 5	< 5	5	400	< 1	< 1	< 5	< 10	< 2	3.16	15	< 1	< 5	< 5	1.92	< 50	< 30	< 0.2	5.3	< 5
57300	5	< 5	< 2	< 100	3	< 1	< 5	20	< 2	1.77	11	< 1	< 5	< 5	2.72	< 50	< 30	< 0.2	2.0	< 5
57301	< 5	< 5	< 2	700	< 1	< 1	6	10	< 2	2.50	11	< 1	< 5	< 5	2.15	< 50	< 30	< 0.2	6.3	< 5
57302	< 5	< 5	< 2	< 100	< 1	3	< 5	10	< 2	3.29	15	< 1	< 5	< 5	2.95	210	< 30	< 0.2	5.4	< 5
57303	8	< 5	< 2	500	< 1	< 1	< 5	20	< 2	3.02	16	< 1	< 5	< 5	2.31	< 50	< 30	< 0.2	2.7	< 5
57304	< 5	< 5	< 2	600	< 1	< 1	< 5	< 10	< 2	3.18	14	< 1	< 5	< 5	0.94	< 50	< 30	< 0.2	2.9	< 5
57305	< 5	< 5	< 2	700	< 1	< 1	< 5	< 10	< 2	2.40	15	< 1	< 5	< 5	1.63	< 50	< 30	< 0.2	2.6	< 5
57306	< 5	< 5	3	< 100	< 1	< 1	< 5	< 10	< 2	2.58	16	< 1	< 5	< 5	1.76	< 50	40	< 0.2	2.4	< 5
57307	14	< 5	3	500	< 1	< 1	< 5	< 10	< 2	2.69	15	< 1	< 5	< 5	1.85	< 50	70	< 0.2	2.3	< 5
57308	< 5	< 5	< 2	< 100	< 1	< 1	< 5	20	< 2	2.65	14	< 1	< 5	< 5	2.94	< 50	< 30	< 0.2	2.4	< 5
57309	< 5	< 5	14	500	< 1	6	26	10	< 2	7.78	2	< 1	< 5	< 5	1.78	< 50	< 30	< 0.2	27.8	< 5
57310	< 5	5	< 2	< 100	< 1	5	28	< 10	< 2	8.86	3	< 1	< 5	< 5	1.55	< 50	< 30	< 0.2	29.7	< 5

Activation Laboratories Ltd. Report: A10-6253 (I) rev 1

Analyte Symbol	Sn	Sr	Ta	Th	U	W	Zn	La	Ce	Nd	Sm	Eu	Tb	Yb	Lu	Mass
Unit Symbol	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	g
Detection Limit	0.05	0.1	1	0.5	0.5	4	50	1	3	5	0.1	0.2	0.5	0.2	0.05	
Analysis Method	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA
57281	< 0.05	< 0.1	< 1	2.0	< 0.5	< 4	230	12	32	13	4.5	1.4	0.9	4.7	0.76	32.2
57282	< 0.05	< 0.1	3	6.7	2.3	< 4	70	31	72	21	6.1	1.5	0.8	6.8	1.06	30.9
57283	< 0.05	< 0.1	< 1	0.8	< 0.5	10	190	10	26	25	4.8	1.7	< 0.5	3.9	0.79	33.2
57284 STAND	< 0.05	< 0.1	< 1	5.2	2.6	23	1900	3	10	5	0.3	0.2	< 0.5	0.3	< 0.05	28.0
57285	< 0.05	< 0.1	< 1	0.9	< 0.5	< 4	190	11	34	24	5.8	1.9	1.2	7.3	0.82	34.0
57286	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	12	31	12	4.7	2.5	1.2	4.6	0.85	34.8
57287	< 0.05	< 0.1	< 1	0.9	< 0.5	4	160	9	23	18	4.7	1.4	0.9	4.1	0.33	33.6
57288	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	110	4	18	12	3.1	1.7	0.9	8.9	1.15	38.5
57289	< 0.05	< 0.1	< 1	7.5	< 0.5	< 4	< 50	43	109	35	12.3	2.8	2.4	17.5	2.65	30.5
57290	< 0.05	< 0.1	< 1	5.8	2.5	< 4	< 50	29	68	27	8.4	2.1	1.7	10.6	1.61	35.8
57291	< 0.05	< 0.1	< 1	4.1	< 0.5	6	< 50	46	109	33	8.2	2.1	0.9	3.4	0.45	33.9
57292	< 0.05	< 0.1	< 1	1.5	< 0.5	< 4	90	9	24	7	3.7	2.0	0.7	3.1	0.11	36.0
57293	< 0.05	< 0.1	3	1.4	< 0.5	< 4	150	12	31	14	5.5	2.2	< 0.5	5.1	0.54	37.2
57294	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	6	15	10	2.5	1.2	0.6	3.3	0.31	33.5
57295	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	8	21	< 5	2.5	1.4	< 0.5	3.2	< 0.05	34.0
57296	< 0.05	< 0.1	< 1	3.2	< 0.5	< 4	< 50	23	55	19	8.9	2.6	2.0	12.5	2.00	30.8
57297	< 0.05	< 0.1	< 1	2.1	2.3	< 4	< 50	22	61	40	8.9	2.6	1.8	11.5	1.73	31.7
57298	< 0.05	< 0.1	2	3.8	< 0.5	< 4	< 50	25	69	45	9.4	2.4	1.6	12.7	2.02	31.0
57299	0.08	< 0.1	< 1	5.8	2.3	< 4	< 50	56	134	65	16.6	3.8	2.9	18.5	2.74	33.2
57300	< 0.05	< 0.1	< 1	5.7	< 0.5	< 4	< 50	41	95	40	11.4	2.6	1.9	13.1	1.98	30.3
57301	< 0.05	< 0.1	< 1	8.2	2.3	< 4	< 50	49	105	50	11.3	3.0	1.5	13.6	2.23	32.6
57302	< 0.05	< 0.1	< 1	5.8	2.3	< 4	< 50	28	74	44	11.9	2.7	2.8	18.7	2.96	30.1
57303	< 0.05	< 0.1	3	8.1	2.5	< 4	< 50	50	115	41	13.9	2.9	3.1	18.8	2.79	31.0
57304	< 0.05	< 0.1	< 1	6.7	1.7	< 4	< 50	41	99	45	12.2	2.7	2.3	17.5	2.74	31.9
57305	< 0.05	< 0.1	< 1	7.3	2.9	< 4	100	50	125	53	14.2	3.1	3.0	20.3	3.01	32.3
57306	< 0.05	< 0.1	5	7.3	< 0.5	< 4	< 50	48	110	45	13.4	2.3	2.7	21.2	3.20	30.3
57307	< 0.05	< 0.1	< 1	7.3	< 0.5	< 4	< 50	50	120	59	13.8	2.8	2.6	20.3	3.00	32.7
57308	< 0.05	< 0.1	4	6.8	3.2	< 4	< 50	44	99	52	12.9	2.6	2.7	17.5	2.63	32.2
57309	< 0.05	< 0.1	< 1	0.8	< 0.5	< 4	160	9	25	< 5	4.1	1.4	0.9	4.4	0.47	40.1
57310	< 0.05	< 0.1	3	< 0.5	< 0.5	< 4	180	13	28	19	5.8	2.1	< 0.5	5.6	0.56	34.4

All pulverized entirely

Activation Laboratories Ltd.

Report: A10-6253 (I) rev 1

Neutron Activation ~ 30g

Analyte Symbol	Au	Ag	As	Ba	Br	Ca	Co	Cr	Cs	Fe	Hf	Hg	Ir	Mo	Na	Ni	Rb	Sb	Sc	Se
Unit Symbol	ppb	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	%	ppm	ppm	ppm	ppm	
Detection Limit	5	5	2	100	1	1	5	10	2	0.02	1	1	5	5	0.05	50	30	0.2	0.1	5
Analysis Method	INAA	INAA	INAA	INAA	INAA															
57311	<5	9	3	<100	<1	5	32	<10	5	9.90	2	<1	<5	<5	1.58	<50	<30	<0.2	34.1	<5
57312	<5	<5	<2	<100	<1	4	29	<10	<2	9.36	2	<1	<5	<5	1.07	<50	<30	<0.2	31.5	<5
57313	<5	<5	3	<100	<1	5	27	<10	<2	9.00	<1	<1	<5	<5	1.38	<50	<30	<0.2	26.3	<5
57314 missing																				
57315	<5	<5	5	<100	<1	2	45	<10	<2	9.72	2	<1	<5	<5	1.29	<50	<30	<0.2	34.7	<5
57316	<5	<5	4	<100	<1	9	23	<10	<2	6.26	<1	<1	<5	<5	0.08	<50	<30	<0.2	22.2	<5
57317	<5	<5	3	<100	<1	6	27	<10	<2	7.44	2	<1	<5	<5	1.60	<50	<30	<0.2	23.6	<5
57318	<5	<5	3	<100	<1	4	39	<10	<2	9.52	3	<1	<5	<5	1.99	<50	<30	0.4	33.0	<5
57319	<5	<5	<2	<100	<1	3	35	<10	<2	8.67	3	<1	<5	<5	<0.05	<50	<30	0.3	32.0	<5
57320	<5	<5	9	200	<1	7	22	<10	<2	5.01	<1	<1	<5	<5	<0.05	<50	30	<0.2	21.1	<5
57321	<5	<5	3	400	2	3	6	<10	<2	2.80	9	<1	<5	<5	0.67	<50	50	<0.2	6.6	<5
57322	<5	<5	22	<100	<1	<1	21	10	<2	3.83	<1	<1	<5	<5	<0.05	<50	30	1.0	16.1	<5
57323	<5	<5	33	<100	<1	4	42	<10	<2	8.93	2	<1	<5	7	0.25	<50	<30	1.2	34.2	<5
57324	<5	<5	<2	300	<1	5	35	<10	<2	8.35	2	<1	<5	<5	1.37	<50	<30	<0.2	30.5	<5
57325	<5	<5	<2	200	<1	5	28	<10	<2	5.13	<1	<1	<5	<5	0.56	<50	<30	0.3	18.8	<5
57326	8	<5	5	<100	<1	5	37	<10	<2	6.64	2	<1	<5	<5	1.25	<50	<30	<0.2	19.5	<5
57327	<5	<5	9	<100	<1	6	54	10	3	8.59	2	<1	<5	<5	1.61	<50	<30	<0.2	25.8	<5
57328	<5	<5	4	<100	<1	4	40	<10	<2	9.01	3	<1	<5	<5	1.78	<50	<30	<0.2	32.0	<5
57329	<5	<5	7	<100	<1	7	34	<10	<2	7.30	2	<1	<5	<5	1.79	<50	<30	<0.2	25.1	<5
57330	<5	<5	7	200	2	9	14	<10	<2	3.62	<1	<1	<5	<5	0.18	<50	<30	<0.2	18.9	<5
57331	<5	<5	6	<100	<1	4	36	<10	<2	8.07	2	<1	<5	<5	1.90	<50	30	<0.2	29.4	<5
57332 STANDARD	190	<5	50	600	<1	4	64	8670	6	6.60	3	<1	35	<5	1.45	1510	100	2.0	26.7	<5

Activation Laboratories Ltd. Report: A10-6253 (I) rev 1

Analyte Symbol	Sn	Sr	Ta	Th	U	W	Zn	La	Ce	Nd	Sm	Eu	Tb	Yb	Lu	Mass
Unit Symbol	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	g
Detection Limit	0.05	0.1	1	0.5	0.5	4	50	1	3	5	0.1	0.2	0.5	0.2	0.05	
Analysis Method	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA
57311	< 0.05	< 0.1	< 1	1.7	< 0.5	< 4	< 50	13	32	23	6.0	2.0	< 0.5	5.5	0.52	36.3
57312	< 0.05	< 0.1	< 1	1.0	< 0.5	< 4	< 50	13	33	21	6.3	2.3	1.2	5.4	0.66	36.5
57313	< 0.05	< 0.1	3	1.1	< 0.5	< 4	190	11	29	18	5.4	1.9	< 0.5	4.8	0.44	36.1
57314 missing																
57315	0.11	< 0.1	< 1	1.0	< 0.5	< 4	170	6	15	< 5	2.5	1.3	< 0.5	3.9	0.50	31.9
57316	< 0.05	< 0.1	< 1	0.7	< 0.5	< 4	270	5	16	8	2.3	1.1	0.5	2.9	0.46	33.7
57317	< 0.05	< 0.1	< 1	1.1	< 0.5	< 4	130	4	10	< 5	1.8	1.4	< 0.5	2.4	0.43	32.5
57318	< 0.05	< 0.1	3	0.7	< 0.5	< 4	190	7	22	13	2.6	1.7	< 0.5	3.3	0.22	35.5
57319	< 0.05	< 0.1	< 1	1.0	< 0.5	30	80	6	18	9	2.9	1.2	0.7	4.4	0.41	35.5
57320	< 0.05	< 0.1	< 1	1.2	< 0.5	18	60	9	22	11	3.8	1.9	0.7	4.5	0.36	32.0
57321	< 0.05	< 0.1	3	5.3	< 0.5	< 4	< 50	32	77	37	8.6	2.1	1.6	11.9	1.90	31.9
57322	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	110	3	9	< 5	1.3	0.8	< 0.5	2.0	0.30	32.7
57323	< 0.05	< 0.1	< 1	1.0	< 0.5	< 4	160	5	16	11	2.1	1.5	< 0.5	3.1	0.20	32.9
57324	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	5	16	11	2.1	1.4	0.5	2.8	0.20	33.7
57325	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	210	5	14	6	2.0	1.0	0.5	2.0	0.34	35.2
57326	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	4	9	< 5	1.7	0.9	< 0.5	2.5	0.48	36.0
57327	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	5	11	13	2.0	1.0	< 0.5	2.5	0.13	34.8
57328	< 0.05	< 0.1	< 1	1.0	< 0.5	< 4	< 50	6	17	13	2.4	1.3	< 0.5	3.4	0.55	32.4
57329	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	130	5	12	< 5	2.0	1.3	< 0.5	2.5	0.09	35.3
57330	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	4	11	10	1.9	1.6	< 0.5	2.6	0.12	33.6
57331	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	5	13	9	2.1	1.2	< 0.5	2.7	0.13	38.8
57332 STAND	< 0.05	< 0.1	< 1	8.8	< 0.5	6	150	21	47	11	4.2	1.2	< 0.5	1.8	0.18	30.4

Activation Laboratories Ltd. Report: A10-6253 (I) rev 1

Activation Laboratories Ltd. Report: A10-6253 (i) rev 1

Quality Analysis ...



Innovative Technologies

Date Submitted: 30-Sep-10
Invoice No.: A10-6842
Invoice Date: 18-Nov-10
Your Reference: CP15-DAXL

CLAIM POST RESOURCES INC
39-630 RIVERPARK ROAD
TIMMINS ON P4P 1B4
Canada

ATTN: Herman Daxl

45 NR HALF CORE
2 PULP STANDARDS

CERTIFICATE OF ANALYSIS

47 Rock samples were submitted for analysis. All pulverized entirely.
The following analytical package was requested Code ID INAA(INAAGEO) Neutron Activation ~30g

REPORT **A10-6842**

Last of CP-10-15

This report may be reproduced without our consent. If only selected portions of the report are reproduced, permission must be obtained. If no instructions were given at time of sample submittal regarding excess material, it will be discarded within 90 days of this report. Our liability is limited solely to the analytical cost of these analyses. Test results are representative only of material submitted for analysis.

Notes:

For values exceeding the upper limits we recommend assays.

CERTIFIED BY :

A handwritten signature in black ink, appearing to read "Emmanuel Eseme".

Emmanuel Eseme , Ph.D.
Quality Control

ACTIVATION LABORATORIES LTD.

1336 Sandhill Drive, Ancaster, Ontario Canada L9G 4V5 TELEPHONE +1.905.648.9611 or
+1.888.228.5227 FAX +1.905.648.9613
E-MAIL ancaster@actlabsint.com ACTLABS GROUP WEBSITE <http://www.actlabsint.com>

All pulverized entirely

Activation Laboratories Ltd.

Report: A10-6842 rev 1

Neutron Activation ~ 30 g

Analyte Symbol	Au	Ag	As	Ba	Br	Ca	Co	Cr	Cs	Fe	Hf	Hg	Ir	Mo	Na	Ni	Rb	Sb	Sc	Se	
Unit Symbol	ppb	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	%	ppm	ppm	ppm	ppm		
Detection Limit	5	5	2	100	1	1	5	10	2	0.02	1	1	5	5	0.05	50	30	0.2	0.1		
Analysis Method	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA		
57333	< 5	< 5	< 2	< 100	< 1	7	39	< 10	< 2	9.20	2	< 1	< 5	< 5	1.61	< 50	< 30	0.2	32.0	< 5	
57334	< 5	< 5	< 2	< 100	< 1	10	40	< 10	< 2	9.27	2	< 1	< 5	< 5	1.06	< 50	60	< 0.2	29.8	< 5	
57335	< 5	< 5	6	< 100	< 1	9	63	30	< 2	9.76	2	< 1	< 5	< 5	0.97	< 50	< 30	0.4	41.3	< 5	
57336	< 5	< 5	< 2	600	< 1	6	16	10	< 2	5.47	2	< 1	< 5	< 5	0.07	< 50	< 30	< 0.2	20.3	< 5	
57337	< 5	< 5	< 2	600	< 1	7	10	< 10	< 2	4.98	< 1	< 1	< 5	< 5	0.09	< 50	30	< 0.2	11.9	< 5	
57338	vs. 14	285	< 5	< 2	< 100	< 1	9	26	< 10	< 2	6.40	1	< 1	< 5	< 5	1.74	< 50	< 30	< 0.2	18.1	< 5
57339	< 5	< 5	11	< 100	< 1	7	60	< 10	< 2	9.13	2	< 1	< 5	< 5	1.95	< 50	< 30	< 0.2	24.8	< 5	
57340	< 5	< 5	7	400	< 1	6	56	< 10	3	8.84	< 1	< 1	< 5	< 5	0.32	< 50	< 30	< 0.2	18.2	< 5	
57341	< 5	< 5	< 2	< 100	< 1	10	21	< 10	< 2	5.23	< 1	< 1	< 5	< 5	0.49	< 50	< 30	< 0.2	6.4	< 5	
57342	< 5	< 5	< 2	< 100	2	7	26	< 10	< 2	6.10	< 1	< 1	< 5	< 5	0.26	< 50	< 30	< 0.2	8.2	< 5	
57343	17	< 5	< 2	< 100	< 1	5	30	< 10	< 2	7.36	2	< 1	< 5	< 5	2.10	< 50	< 30	< 0.2	24.3	< 5	
57344	< 5	< 5	< 2	< 100	5	7	12	10	< 2	6.13	2	< 1	< 5	< 5	1.44	< 50	80	< 0.2	17.3	< 5	
57345	80	< 5	16	< 100	< 1	9	29	70	< 2	7.32	2	< 1	< 5	< 5	0.20	< 50	40	< 0.2	29.1	< 5	
57346	< 5	< 5	< 2	< 100	4	5	18	10	< 2	5.14	2	< 1	< 5	< 5	0.98	< 50	< 30	0.3	22.3	< 5	
57347	< 5	< 5	5	< 100	< 1	5	42	< 10	< 2	11.00	2	< 1	< 5	< 5	1.18	< 50	< 30	< 0.2	35.9	< 5	
57348	< 5	< 5	< 2	< 100	< 1	7	46	< 10	< 2	9.79	2	< 1	< 5	< 5	1.73	< 50	< 30	< 0.2	37.1	< 5	
57349	< 5	< 5	< 2	< 100	< 1	7	38	< 10	4	10.10	2	< 1	< 5	< 5	1.62	< 50	< 30	< 0.2	34.8	< 5	
57350	96	< 5	29	< 100	< 1	6	48	< 10	< 2	9.07	2	< 1	< 5	< 5	< 0.05	< 50	< 30	0.9	23.3	< 5	
57351	21	< 5	19	400	< 1	6	40	< 10	< 2	9.81	2	< 1	< 5	< 5	0.59	< 50	40	0.4	29.9	< 5	
57352	< 5	< 5	< 2	< 100	< 1	7	48	< 10	< 2	12.30	2	< 1	< 5	< 5	1.57	< 50	< 30	< 0.2	39.1	< 5	
57353	< 5	< 5	5	< 100	< 1	5	52	< 10	< 2	13.00	2	< 1	< 5	< 5	1.12	< 50	< 30	< 0.2	38.0	< 5	
57354	< 5	< 5	< 2	< 100	< 1	8	45	< 10	< 2	11.80	3	< 1	< 5	< 5	1.89	< 50	< 30	0.6	37.5	< 5	
57355	< 5	< 5	< 2	< 100	< 1	6	49	< 10	5	13.50	2	< 1	< 5	< 5	1.08	< 50	< 30	< 0.2	32.8	< 5	
✓ 57356 STAND H3-2120	< 5	< 2	< 100	4	< 1	21	150	3	4.86	2	< 1	< 5	33	0.18	50	< 30	15.6	11.6	17		
57357	< 5	< 5	10	400	< 1	3	40	< 10	< 2	10.70	3	< 1	< 5	< 5	1.30	< 50	< 30	< 0.2	30.9	< 5	
57358	< 5	< 5	< 2	< 100	< 1	6	37	< 10	< 2	9.71	2	< 1	< 5	< 5	1.96	< 50	< 30	< 0.2	27.6	< 5	
57359	< 5	< 5	18	400	< 1	8	28	< 10	< 2	7.61	2	< 1	< 5	< 5	0.07	< 50	40	< 0.2	15.3	< 5	
57360	< 5	< 5	31	< 100	< 1	6	35	< 10	< 2	9.22	2	< 1	< 5	< 5	< 0.05	< 50	< 30	< 0.2	27.7	< 5	
57361	< 5	< 5	< 2	< 100	< 1	7	44	< 10	< 2	10.30	2	< 1	< 5	< 5	2.24	< 50	< 30	< 0.2	31.2	< 5	
57362	< 5	< 5	< 2	< 100	< 1	6	39	< 10	< 2	10.50	2	< 1	< 5	< 5	2.03	< 50	< 30	0.6	33.6	< 5	

Activation Laboratories Ltd.

Report: A10-6842 rev 1

Analyte Symbol	Au	Ag	As	Ba	Br	Ca	Co	Cr	Cs	Fe	Hf	Hg	Ir	Mo	Na	Ni	Rb	Sb	Sc	Se
Unit Symbol	ppb	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	%	ppm	ppm	ppm	ppm	
Detection Limit	5	5	2	100	1	1	5	10	2	0.02	1	1	5	5	0.05	50	30	0.2	0.1	
Analysis Method	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	
57363	< 5	< 5	< 2	600	< 1	7	35	< 10	< 2	11.00	2	< 1	< 5	< 50	0.22	< 50	40	0.4	35.0	< 5
57364	< 5	< 5	15	700	< 1	5	44	< 10	< 2	11.80	2	< 1	< 5	< 50	< 0.05	< 50	50	< 0.2	31.2	< 5
57365	< 5	< 5	17	500	< 1	6	41	< 10	< 2	12.00	2	< 1	< 5	< 50	0.86	< 50	< 30	0.3	32.3	< 5
57366	< 5	< 5	< 2	400	< 1	4	41	< 10	< 2	10.10	2	< 1	< 5	< 50	1.72	< 50	< 30	< 0.2	29.7	< 5
57367	< 5	< 5	5	600	< 1	7	36	< 10	< 2	10.70	3	< 1	< 5	< 50	2.30	< 50	< 30	< 0.2	31.8	< 5
57368	< 5	< 5	< 2	< 100	< 1	9	31	10	< 2	8.35	2	< 1	< 5	< 50	1.68	< 50	< 30	< 0.2	24.0	< 5
57369	< 5	< 5	14	< 100	< 1	6	37	< 10	< 2	10.70	2	< 1	< 5	< 50	1.05	< 50	< 30	< 0.2	27.4	< 5
57370	< 5	< 5	13	< 100	< 1	6	32	< 10	< 2	9.60	2	< 1	< 5	< 50	0.38	< 50	< 30	0.6	27.7	< 5
57371	< 5	< 5	15	400	1	6	39	< 10	< 2	10.40	2	< 1	< 5	< 50	0.08	< 50	80	0.9	30.5	< 5
57372	< 5	< 5	< 2	< 100	< 1	6	43	< 10	< 2	11.50	2	< 1	< 5	< 50	1.48	< 50	< 30	< 0.2	31.4	< 5
57373	< 5	< 5	16	600	< 1	6	37	< 10	< 2	9.84	1	< 1	< 5	< 50	1.64	< 50	< 30	< 0.2	27.9	< 5
✓ 57374 STAND 136 220 ✓	< 5	61	800	< 1	7	77	10400	6	8.29	2	< 1	30	15	1.69	1820	100	2.5	24.5	< 5	
57375	< 5	< 5	40	< 100	< 1	6	48	< 10	< 2	9.53	2	< 1	< 5	< 50	2.28	< 50	< 30	0.4	34.2	< 5
57376	< 5	< 5	12	< 100	< 1	6	49	< 10	< 2	10.50	2	< 1	< 5	< 50	1.39	< 50	< 30	< 0.2	28.8	< 5
57377	< 5	< 5	52	500	< 1	< 1	35	60	< 2	7.94	4	< 1	< 5	< 50	0.25	< 50	60	1.2	27.4	< 5
57378	< 5	< 5	37	< 100	< 1	< 1	41	50	< 2	8.46	5	< 1	< 5	< 50	0.80	< 50	< 30	1.3	29.6	< 5
57379	< 5	< 5	< 2	< 100	< 1	5	41	50	5	10.10	5	< 1	< 5	< 50	1.53	< 50	< 30	0.5	35.9	< 5

All pulverized entirely

Activation Laboratories Ltd.

Report: A10-6842 rev 1

Neutron Activation ~30 g

Analyte Symbol	Sn	Sr	Ta	Th	U	W	Zn	La	Ce	Nd	Sm	Eu	Tb	Yb	Lu	Mass
Unit Symbol	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	g
Detection Limit	0.05	0.1	1	0.5	0.5	4	50	1	3	5	0.1	0.2	0.5	0.2	0.05	
Analysis Method	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	
57333	< 0.05	< 0.1	< 1	< 0.5	1.6	< 4	190	6	16	< 5	2.4	1.6	< 0.5	3.1	0.64	40.2
57334	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	290	6	20	< 5	2.5	1.8	< 0.5	3.2	0.55	30.3
57335	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	7	20	19	3.0	1.6	< 0.5	4.1	0.65	30.6
57336	< 0.05	< 0.1	< 1	0.5	< 0.5	< 4	< 50	4	14	< 5	1.6	1.5	0.6	2.6	0.40	33.8
57337	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	80	3	10	11	1.2	1.1	< 0.5	2.0	0.10	34.0
57338	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	210	5	12	11	2.0	1.2	< 0.5	2.3	0.43	38.0
57339	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	6	22	< 5	2.4	1.5	< 0.5	3.3	0.59	31.1
57340	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	140	3	11	< 5	1.4	1.4	< 0.5	1.8	0.34	36.4
57341	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	2	7	< 5	0.8	0.8	< 0.5	1.2	0.23	36.1
57342	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	130	1	4	< 5	0.5	0.3	< 0.5	1.0	0.17	35.6
57343	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	6	15	12	2.3	1.5	< 0.5	2.6	0.46	36.1
57344	< 0.05	< 0.1	< 1	0.9	< 0.5	15	120	4	15	< 5	2.1	1.9	< 0.5	3.3	0.62	35.4
57345	< 0.05	< 0.1	< 1	2.6	< 0.5	27	< 50	30	82	38	7.9	3.5	< 0.5	3.2	0.58	32.0
57346	< 0.05	< 0.1	< 1	0.7	< 0.5	18	< 50	5	11	10	1.9	1.1	1.0	2.5	0.38	33.0
57347	< 0.05	< 0.1	< 1	0.8	< 0.5	< 4	160	6	14	< 5	2.3	1.0	< 0.5	3.0	0.51	36.6
57348	< 0.05	< 0.1	2	< 0.5	1.9	< 4	160	7	20	10	2.8	1.7	< 0.5	3.8	0.62	35.1
57349	< 0.05	< 0.1	< 1	1.3	< 0.5	< 4	250	15	44	22	7.6	2.6	1.4	6.7	1.06	36.0
57350	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	19700	9	24	16	4.8	2.0	< 0.5	4.2	0.69	30.9
57351	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	240	13	35	18	6.4	2.8	1.3	5.7	0.86	35.6
57352	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	220	12	37	19	6.3	2.4	< 0.5	5.8	0.93	30.3
57353	< 0.05	< 0.1	< 1	1.9	< 0.5	< 4	290	14	39	25	7.0	2.8	1.6	6.0	0.95	38.8
57354	< 0.05	< 0.1	< 1	< 0.5	2.8	< 4	440	18	55	34	9.2	3.6	< 0.5	7.7	1.19	30.8
57355	< 0.05	< 0.1	< 1	1.4	< 0.5	< 4	460	10	25	16	5.3	1.8	< 0.5	4.7	0.70	30.6
✓ 57356 STAND H3	< 0.05	< 0.1	< 1	6.6	< 0.5	34	2220	4	10	< 5	0.7	< 0.2	< 0.5	0.6	0.14	29.1
57357	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	430	11	36	15	5.4	1.7	< 0.5	4.6	0.80	33.3
57358	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	150	10	27	14	5.4	2.1	1.2	4.6	0.82	36.1
57359	< 0.05	< 0.1	< 1	1.5	< 0.5	< 4	160	13	33	15	4.8	1.5	< 0.5	4.6	0.70	32.5
57360	< 0.05	< 0.1	1	< 0.5	< 0.5	< 4	290	12	34	19	5.4	2.1	1.1	5.5	0.90	33.7
57361	< 0.05	< 0.1	< 1	1.1	< 0.5	5	190	13	36	19	6.2	1.9	< 0.5	5.5	0.93	32.3
57362	< 0.05	< 0.1	2	1.4	< 0.5	< 4	< 50	13	38	17	6.8	2.2	1.2	5.7	0.93	30.5

Activation Laboratories Ltd. Report: A10-6842 rev 1

Analyte Symbol	Sn	Sr	Ta	Th	U	W	Zn	La	Ce	Nd	Sm	Eu	Tb	Yb	Lu	Mass
Unit Symbol	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	g
Detection Limit	0.05	0.1	1	0.5	0.5	4	50	1	3	5	0.1	0.2	0.5	0.2	0.05	
Analysis Method	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA
57363	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	280	13	35	17	6.6	2.8	1.5	5.6	0.95	32.5
57364	< 0.05	< 0.1	< 1	0.9	< 0.5	< 4	7630	13	38	33	6.5	2.5	1.5	5.4	0.47	30.0
57365	< 0.05	< 0.1	< 1	1.0	< 0.5	< 4	320	13	38	21	6.5	2.3	< 0.5	6.2	0.93	33.6
57366	< 0.05	< 0.1	3	1.5	1.5	7	210	12	35	27	5.9	2.1	< 0.5	4.9	0.47	36.3
57367	< 0.05	< 0.1	< 1	0.9	1.2	< 4	140	15	39	22	6.8	3.2	1.1	5.7	0.96	30.2
57368	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	150	9	26	16	4.9	1.6	< 0.5	4.3	0.74	36.4
57369	< 0.05	< 0.1	< 1	1.8	< 0.5	< 4	230	11	31	< 5	5.4	1.9	1.2	4.8	0.81	34.2
57370	< 0.05	< 0.1	2	1.0	< 0.5	< 4	160	9	27	21	5.5	1.8	1.6	6.5	0.99	30.2
57371	< 0.05	< 0.1	< 1	1.3	1.4	< 4	200	12	32	26	6.1	2.6	< 0.5	5.7	0.88	35.8
57372	< 0.05	< 0.1	< 1	2.1	< 0.5	< 4	1630	11	28	19	5.3	1.4	1.0	4.6	0.77	37.8
57373	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	840	11	31	20	5.5	1.8	1.3	4.7	0.80	34.7
✓ 57374 STAND 136 - 0.05 < 0.1 10.5 < 0.5 < 4 < 50 13.3 26 59 26 4.9 1.3 < 0.5 2.5 0.27 28.3																
57375	< 0.05	< 0.1	< 1	0.9	< 0.5	4	240	11	34	18	6.3	3.1	1.6	8.0	1.20	30.6
57376	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	190	11	29	18	5.2	1.7	1.1	5.3	0.76	36.3
57377	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	1330	10	26	17	3.5	1.5	< 0.5	5.8	0.95	35.1
57378	< 0.05	< 0.1	< 1	2.0	< 0.5	< 4	970	10	22	12	4.1	1.7	0.6	5.8	0.94	30.6
57379	< 0.05	< 0.1	< 1	< 0.5	< 0.5	< 4	< 50	13	36	< 5	5.2	1.7	< 0.5	6.3	1.09	36.4

Activation Laboratories Ltd.

Report: A10-6842 rev 1

Quality Control		Au	Ag	As	Ba	Br	Ca	Co	Cr	Cs	Fe	Hf	Hg	Ir	Mo	Na	Ni	Rb	Sb	Sc
Analyte Symbol	Unit Symbol	ppb	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm
Detection Limit	5	5	2	100	1	1	5	10	2	0.02	1	1	5	5	0.05	50	30	0.2	0.1	
Analysis Method	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	
DMMAS 111 Meas	1670		1470	1100			38	50		2.78					1.88				5.80	
DMMAS 111 Cert	1670		1450	1140			34	52		2.79					1.87				5.80	
DMMAS 111 Meas	1670		1510	1200			38	50		2.87					1.93				6.00	
DMMAS 111 Cert	1670		1450	1140			34	52		2.79					1.87				5.80	
57362 Orig	< 5	< 5	< 2	< 100	< 1	6	39	< 10	< 2	10.50	2	< 1	< 5	< 5	2.03	< 50	< 30	0.6	33.60	
57362 Split	< 5	< 5	< 2	< 100	< 1	5	36	< 10	< 2	10.50	2	< 1	< 5	< 5	1.98	< 50	< 30	0.6	32.70	
57378 Orig	< 5	< 5	37	< 100	< 1	< 1	41	50	< 2	8.46	5	< 1	< 5	< 5	0.80	< 50	< 30	1.3	29.60	
57378 Split	< 5	< 5	37	< 100	< 1	< 1	40	60	< 2	8.26	5	< 1	< 5	< 5	0.77	< 50	< 30	1.4	29.50	

Activation Laboratories Ltd.

Report: A10-6842 rev 1

Quality Control

Analyte Symbol	Sn	Sr	Ta	Th	U	W	Zn	La	Ce	Nd	Sm	Eu	Tb	Yb	Lu	Moss
Unit Symbol	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	g
Detection Limit	0.05	0.1	1	0.5	0.5	4	50	1	3	5	0.1	0.2	0.5	0.2	0.05	
Analysis Method	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA	INAA
DMMAS 111 Meas					14.10			15.00	23.00		1.70					
DMMAS 111 Cert					14.00			14.00	19.30		1.90					
DMMAS 111 Meas					14.70			15.00	22.00		1.70					
DMMAS 111 Cert					14.00			14.00	19.30		1.90					
57362 Orig	< 0.05	< 0.1	2	1.4	< 0.5	< 4	< 50	13.00	38.00	17	6.80	2.2	1.2	5.7	0.93	30.5
57362 Split	< 0.05	< 0.1	3	1.4	< 0.5	< 4	< 50	13.00	34.00	16	6.30	2.0	1.4	5.5	0.88	34.3
57378 Orig	< 0.05	< 0.1	< 1	2.0	< 0.5	< 4	970	10.00	22.00	12	4.10	1.7	0.6	5.8	0.94	30.6
57378 Split	< 0.05	< 0.1	< 1	2.1	< 0.5	< 4	920	9.00	23.00	12	3.80	1.6	0.7	5.7	1.02	32.9



ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: 604 984 0221 Fax: 604 984 0218 www.alsglobal.com

To: CLAIM POST RESOURCES INC.
141 ADELAIDE STREET WEST
SUITE 903
TORONTO ON M5H 3L5

Page: 1
Finalized Date: 10- NOV- 2010
Account: CLAPST

CERTIFICATE VA10157685

Project: CP4 PULP- DAXL

P.O. No.:

This report is for 32 Pulp samples submitted to our lab in Vancouver, BC, Canada on 26-OCT-2010.

The following have access to data associated with this certificate:

HERMANN DAXL

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI- 21	Received Sample Weight
LOG- 24	Pulp Login - Rcd w/o Barcode
LOG- QC	QC Test on Received Samples

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
ME- ICP41a	High Grade Aqua Regia ICP- AES	ICP- AES
ME- OG46	Ore Grade Elements - AquaRegia	ICP- AES
Zn- OG46	Ore Grade Zn - Aqua Regia	VARIABLE
ME- MS81	38 element fusion ICP- MS	ICP- MS
ME- XRF11	Iron Ores by fusion/XRF	XRF
OA- GRA05t	Multi- temperature LOI	TGA
PGM- ICP23	Pt, Pd, Au 30g FA ICP	ICP- AES

Repeat analyses from pulps
4- Corners CP-10-12 to 15

To: CLAIM POST RESOURCES INC.
ATTN: HERMANN DAXL
141 ADELAIDE STREET WEST
SUITE 903
TORONTO ON M5H 3L5

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature:

Colin Ramshaw, Vancouver Laboratory Manager



ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: 604 984 0221 Fax: 604 984 0218 www.alsglobal.com

To: CLAIM POST RESOURCES INC
141 ADELAIDE STREET WEST
SUITE 903
TORONTO ON M5H 3L5

Page: 2 - A
Total # Pages: 2 (A - G)
Finalized Date: 10- NOV- 2010
Account: CLAPST

30 g Fire Assay

Aqua Regia

Project: CP4 PULP- DAXL

CERTIFICATE OF ANALYSIS VA10157685



ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: 604 984 0221 Fax: 604 984 0218 www.alsglobal.com

To: CLAIM POST RESOURCES INC.
141 ADELAIDE STREET WEST
SUITE 903
TORONTO ON M5H 3L5

Page: 2 - B
Total # Pages: 2 (A - G)
Finalized Date: 10- NOV- 2010
Account: CLAPST

Aqua Regia

Project: CP4 PULP- DAXL

CERTIFICATE OF ANALYSIS VA10157685



ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: 604 984 0221 Fax: 604 984 0218 www.alsglobal.com

To: CLAIM POST RESOURCES INC.
141 ADELAIDE STREET WEST
SUITE 903
TORONTO ON M5H 3L\$

Page: 2 - C
Total # Pages: 2 (A - G)
Finalized Date: 10-NOV-2010
Account: CLAPST

Aqua Regia

Project: CP4 PULP- DAXL

Lithium Borate Fusion

CERTIFICATE OF ANALYSIS VA10157685

Sample Description	Method Analyte Units LOR	ME-ICP41a Sr ppm	ME-ICP41a Th ppm	ME-ICP41a Ti %	ME-ICP41a U ppm	ME-ICP41a V ppm	ME-ICP41a W ppm	ME-ICP41a Zn ppm	Zn-OG46 Zn %	ME-MS81 Ag ppm	ME-MS81 Ba ppm	ME-MS81 Ce ppm	ME-MS81 Co ppm	ME-MS81 Cr ppm	ME-MS81 Cs ppm
51665		43	<100	0.22	<50	<50	64	<50	10500	1	408	33.1	49.4	60	0.39
51667		34	<100	0.22	<50	<50	81	<50	4290						
51668		34	<100	0.27	<50	<50	61	50	>50000	6.74					
51669		80	<100	0.17	<50	<50	34	50	39300						
51938 MAGNETITE DIKE										<1	81.9	21.0	69.1	50	0.64
51983										<1	32.8	126.0	6.2	<10	0.03
57255															
57260															
57263															
57271															
57278															
57286															
57288															
57293															
57295															
57304										<1	392	24.3	42.1	<10	0.45
57310										<1	171.0	43.8	36.2	<10	2.43
57311										<1	62.8	20.1	44.9	<10	0.09
57315															
57318															
57326															
57327															
57333															
57335															
57340															
57350		68	<100	0.36	<50	<50	50	<50	17900						
57353															
57355															
57357		47	<100	0.49	<50	<50	112	<50	470						
57360		62	<100	0.25	<50	<50	49	<50	230						
57364		20	<100	0.45	<50	<50	50	<50	7080						
57379										<1	233	36.5	43.0	60	4.61



ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: 604 984 0221 Fax: 604 984 0218 www.alsglobal.com

To: CLAIM POST RESOURCES INC.
141 ADELAIDE STREET WEST
SUITE 903
TORONTO ON M5H 3L5

Page: 2 - D
Total # Pages: 2 (A - G)
Finalized Date: 10- NOV- 2010
Account: CLAPST

Lithium Borate Fusion

Project: CP4 PULP- DAXL

CERTIFICATE OF ANALYSIS VA10157685

Sample Description	Method Analyte Units LOR	ME- MS81 Cu ppm S	ME- MS81 Dy ppm 0.05	ME- MS81 Er ppm 0.03	ME- MS81 Eu ppm 0.03	ME- MS81 Ga ppm 0.1	ME- MS81 Gd ppm 0.05	ME- MS81 Hf ppm 0.2	ME- MS81 Ho ppm 0.01	ME- MS81 La ppm 0.5	ME- MS81 Lu ppm 0.01	ME- MS81 Mo ppm 2	ME- MS81 Nb ppm 0.2	ME- MS81 Nd ppm 0.1	ME- MS81 Ni ppm 5	ME- MS81 Pb ppm 5
51665		73	8.80	5.06	2.43	19.2	8.18	2.9	1.89	12.2	0.64	<2	8.4	24.6	7	5
51667																
51668																
51669		8	7.68	4.38	1.83	16.3	6.68	2.1	1.66	7.8	0.50	<2	4.4	16.7	<5	<5
51938		199	12.55	6.95	1.49	16.7	13.95	0.6	2.57	51.7	0.65	<2	0.7	65.3	<5	<5
-51989~																
57255																
57260																
57263																
57271																
57278																
57286																
57288																
57293																
57295		138	5.00	3.23	1.91	25.5	4.16	4.9	1.09	10.5	0.51	<2	13.8	14.3	5	<5
57304																
57310																
57311		15	11.20	6.58	2.92	21.1	10.55	3.5	2.42	16.3	0.86	<2	9.4	32.7	<5	<5
57315																
57318		17	5.45	3.40	2.00	24.5	4.27	3.0	1.21	8.0	0.52	<2	7.4	12.9	11	<5
57326																
57327																
57333																
57335																
57340																
57350																
57353																
57355																
57357																
57360																
57364																
57379		42	9.26	5.87	2.26	20.6	7.48	6.0	2.07	14.2	0.89	<2	9.5	24.1	48	<5



ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: 604 984 0221 Fax: 604 984 0218 www.alsglobal.com

To: CLAIM POST RESOURCES INC.
141 ADELAIDE STREET WEST
SUITE 903
TORONTO ON M5H 3L5

Page: 2 - E
Total # Pages: 2 (A - G)
Finalized Date: 10- NOV- 2010
Account: CLAPST

Lithium Borate Fusion

Project: CP4 PULP- DAXL

CERTIFICATE OF ANALYSIS VA10157685

Sample Description	Method Analyte Units LOR	ME- MS81 Pr ppm 0.03	ME- MS81 Rb ppm 0.2	ME- MS81 Sm ppm 0.03	ME- MS81 Sn ppm 1	ME- MS81 Sr ppm 0.1	ME- MS81 Ta ppm 0.1	ME- MS81 Tb ppm 0.01	ME- MS81 Th ppm 0.05	ME- MS81 Tl ppm 0.5	ME- MS81 Tm ppm 0.01	ME- MS81 U ppm 0.05	ME- MS81 V ppm 5	ME- MS81 W ppm 1	ME- MS81 Y ppm 0.5	ME- MS81 Yb ppm 0.03
51665		4.96	39.7	7.47	1	47.7	0.6	1.47	0.85	<0.5	0.66	0.21	145	1	49.1	4.40
51667																
51668																
51669		3.21	9.2	5.63	1	87.9	0.3	1.25	0.68	<0.5	0.58	0.17	51	1	44.7	3.65
51938 MAGNETITE DIKE		15.90	2.9	14.35	1	26.7	<0.1	2.28	1.53	<0.5	0.83	0.16	90	<1	67.9	5.05
51983																
57255																
57260																
57263																
57271																
57278																
57286																
57288																
57293																
57295		3.17	27.5	3.88	4	141.0	1.0	0.80	1.38	<0.5	0.46	0.35	227	1	29.2	3.18
57304																
57310																
57311		6.53	37.5	9.83	2	94.9	0.7	1.87	1.11	<0.5	0.87	0.28	121	<1	63.1	5.83
57315																
57318		2.83	3.8	3.83	1	199.0	0.6	0.83	0.83	<0.5	0.49	0.17	300	<1	31.1	3.45
57326																
57327																
57333																
57335																
57340																
57350																
57353																
57355																
57357																
57360																
57364																
57379		5.18	109.5	7.09	3	89.2	0.6	1.49	1.55	<0.5	0.85	0.39	358	<1	53.5	5.79



ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: 604 984 0221 Fax: 604 984 0218 www.alsglobal.com

To: CLAIM POST RESOURCES INC.
141 ADELAIDE STREET WEST
SUITE 903
TORONTO ON M5H 3L5

Page: 2 - F
Total # Pages: 2 (A - G)
Finalized Date: 10- NOV- 2010
Account: CLAPST

Project: CP4 PULP- DAXL

CERTIFICATE OF ANALYSIS VA10157685



ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: 604 984 0221 Fax: 604 984 0218 www.alsglobal.com

To: CLAIM POST RESOURCES INC.
141 ADELAIDE STREET WEST
SUITE 903
TORONTO ON M5H 3L5

Page: 2 - G
Total # Pages: 2 (A - G)
Finalized Date: 10- NOV- 2010
Account: CLAPST

Iron Ore Fusion

Project: CP4 PULP- DAXL

CERTIFICATE OF ANALYSIS VA10157685

Sample Description	Method Analyte Units LOR	ME-XRF11										
		Na2O	Ni	P	Pb	S	Sn	Sr	TiO2	V	Zn	Zr
		%	%	%	%	%	%	%	%	%	%	%
51665												
51667												
51668												
51669												
51938 MAGNETITE DIKE		0.05	0.013	0.452	0.005	0.002	<0.001	0.003	0.85	0.076	0.005	0.001
57255												
57260												
57263		3.18	<0.001	0.102	<0.001	0.416	<0.001	0.011	3.78	0.027	0.012	0.010
57271		2.26	<0.001	0.720	<0.001	0.194	<0.001	0.006	4.48	0.019	0.011	0.010
57278												
57286												
57288												
57293		2.34	<0.001	0.552	<0.001	0.116	<0.001	0.019	2.74	0.005	0.012	0.010
57295		4.38	<0.001	0.154	<0.001	0.072	<0.001	0.008	5.99	0.018	0.010	0.016
57304												
57310												
57311		2.75	<0.001	0.601	<0.001	0.127	<0.001	0.007	2.96	0.010	0.013	0.013
57315												
57318		3.22	<0.001	0.088	<0.001	0.105	<0.001	0.018	3.49	0.027	0.010	0.011
57326												
57327												
57333												
57335												
57340												
57350												
57353												
57355												
57357												
57360												
57364												
57379		2.29	0.001	0.194	<0.001	0.199	<0.001	0.003	2.56	0.033	0.005	0.022

Certificate Of Analysis

Cattarello Assayers Inc.

475 Railway Street, Timmins



Cattarello Assayers Inc.

Number Of Samples: 9

Client: Claim Post Resources INC.

Job: 459

4-CORNERS DRILLING 2010
KAMISKOTIA

Type Of Sample: Rock

Hermann Daxl

Received Date: December 22, 2010

Processed Date: December 23, 2010

Report Date: January 04, 2011

Test Method: FAAA 30g.

FIRE ASSAY - ATOMIC ABSORPTION
FROM PULPS SUBMITTED.

Sample ID	AU	Au-Dup	Au
	AA	AA	Grav
	Gr/Mt	Gr/Mt	Gr/Mt
	0.005	0.005	0.005
HOLE	=====	=====	=====
CP-10-13	57252	0.007	
	57277	0.258	
14	57279	0.158	
	57297	0.006	
	57299	<0.005	
15	57338 BIG PULP	0.014	
	57396 = 51663	0.049 BIG PULP	
14	57397 STANDARD	2.775 ✓ OREAS 54 Pa vs. 2.90	
	57398 = 51663	0.033 SMALL PULP 0.040	

Approved By Chief Analyst:

Issue Date	Revision Date	Rev #	Owner	Form ID	Page
18/02/2010	18/02/2010	1	Chris Hacquard	ANAL-002	1 Of 1

Legend and Rock Description:

Rock Units:

- B Basalt
FG Fine- to very fine-grained gabbro, usually dark gray with
FGil black specks well visible on dry core. These are ilmenite (il),
subhedral, 0.5 to 2mm, <15% disseminated, or
mFGil magnetite-ilmenite intergrowth when magnetic (mil).
FGsn When altered to sphene (sn) near quartz-veins the gabbro
FGlx is somewhat brownish. When altered to leucoxene (lx)
the pale-buff grains of same habit are visible on wet core.
GG Green medium-grained gabbro, plagioclase is greenish due
to epidote which also occurs as anastamosing veinlets locally.
mGG Usually magnetic (m), with ilmenite but not so apparent,
transitional from mFGil.
G Medium-grained gray gabbro, usually melanocratic with
white plagioclase laths, nonmagnetic, sparse ilmenite but
not apparent. Possibly an older intrusion.
P, GP Pyroxenite, G with local pyroxenite.
S Sandstone, well sorted, rounded, and packed <2mm
clean cemented pale beige quartz. No bedding.
T Tonalite, diffusely medium-grained, variably 10% dark
mafics, probably metamorphosed sandstone.

Structure:


- F30 Fault at 30 degrees to core axis (CA), evidenced by shear,
FZ broken core, or some gouge. FZ is wider fault zone.
Vqc Veins of quartz-calcite. QV >15cm thick.
W Water seam, as reported by drillers, or at limonite alteration.

Minerals:

cp	chalcopyrite	m	magnetic
py	pyrite	il	ilmenite
sl	sphalerite	sn	sphene
mt	magnetite	lx	leucoxene

Main values plotted:

Au Ag in g/t, Cu Zn in %, over m: 0.32Au,2.30Ag,6.35Zn/0.26



TOTAL FIELD MAGNETICS

Base 57000 nT

1:2500, metric grid, contours 100nT,

CLAIM POST RESOURCES INC.

4-Corners Area, Kamiskotia Project.

Excerpt - Daxl - 31 Dec 2010

POLE-DIPOLE

Infinity at L16E-1725N

Filter

*

**

← travel az. 220° straight, current behind

DIPOLE LENGTH : a=25

DIPOLE SPACINGS : n = 8

Comments :

CHARGEABILITY

Interval 1, 10

RESISTIVITY






Logarithmic 1, 1.5, 2, 3, 5, 7.5, 10...

INSTRUMENTS

RECEIVER : ELREC PRO

TRANSMITTER : VIP 3000KWATT

Scale 1:2500



GRYBA-DAXL CLAIMS

INDUCED POLARISATION

TIELINE 1600mE

3rd



Date : NOV 2004

Property : 4-CORNER PROPERTY

Township : this Line in TOWNSHIP ROBB

Survey by : EXSICS EXPLORATION LIMITED

See also TRUE DEPTH and SPECTRAL IP.



CLAIM POST RESOURCES INC.

INDUCED POLARIZATION



LINE 1300 N

Date : JAN./06

Property : FOUR CORNER PROPERTY

Township : ROBB TOWNSHIP

Survey by : EXSICS EXPLORATION LTD.





AIM POST RESOURCES LTD.



DUCED POLARIZATION

INE 1225 N

: JAN./ 06
ng Division: PORCUPINE
ship : ROBB TOWNSHIP
ey by : EXSICS EXPLORATION LTD.



CLAIM POST RESOURCES INC.
INDUCED POLARIZATION
LINE 1150 N
Date : NOV./04
Property : FOUR CORNERS PROPERTY
Township : ROBB TOWNSHIP
Survey by : EXSICS EXPLORATION LIMITED



CLAIM POST RESOURCES LTD.

INDUCED POLARIZATION

LINE 1075 N

Date : JANUARY 2006
Property: FOUR CORNER PROPERTY
Township : ROBB TOWNSHIP
Survey by : EXSICS EXPLORATION LTD