

# **Assessment Work Report**

**On Claims 3007492, 1140510, & 4243947**

**Gillies Limit North, Larder Lake Mining Division**

**By AL Kon**

**November 17, 2012**

## Summary

During the late summer and fall of 2012 a Phase 2 exploration program was undertaken on claims 3007492, 4243947 & 1140510 also known as the Hound Chutes Rd claims.

The program consisted of prospecting, mapping, overburden depth testing and mechanical stripping and channel sampling.

A Komatsu 200 excavator with a ditching bucket from Lathem's Excavation Ltd was used for the surface stripping. A 6.5 hp Honda high volume water pump was used for outcrop washing and a Stihl TS 420 Quikcut for channel sampling.

AGAT Labs in Sudbury performed the geochem analysis.

AL Kon of North Cobalt/Haileybury supervised all the work and students from Haileybury School of Mines were hired as laborers. Approximately 165 man hours were spent on this program.

## Index

Introduction .....	.2
Access & Location	
Topographical & Vegetation.....	.2
Geology &	
Property Geology.....	.2
Historical Work &	
Work Program .....	.3
Sampling.....	.4
Daily Logs.....	.5
Pictures.....	.6&7
Recommendations.....	.8
Assay Results.....	Appendix I
Maps.....	Appendix II

## **INTRODUCTION**

This work report on claims in the Hound Chutes Road area has been prepared by Alan Kon of North Cobalt/Haileybury Ontario.

## **PROPERTY LOCATION AND ACCESS**

The claims can be accessed by the Hound Chutes Road, an Ontario Hydro access road that departs south west from the town of Cobalt and follows the eastern side of the Montreal River. The claims are within one Km of the Hound Chutes hydro power dam and the Ragged Chutes dam.

## **TOPOGRAPHY AND VEGETATION**

Maximum relief on the property is approximately 25 metres. Topography is generally rolling with local steep ledges and cliffs. Giroux Creek flows south and westward through the area mapped and into the Montreal River.

Overburden is relatively shallow over the north and south parts of the claims but of unknown depth in the centre. Vegetation on the claims consists mainly of mature mixed forest and locally dense underbrush.

## **REGIONAL AND PROPERTY GEOLOGY**

The claims are located in the southern part of the Cobalt mining camp. Regionally the area is underlain by an N-S trending trough of Huronian metasedimentary rocks (Cobalt Group, Gowganda Formation, Coleman Member - conglomerates) that cover a complex Archean mafic volcanic terrain. In the cobalt area the Archean volcanic and overlying Huronian sediments have been intruded by extensive Nipissing aged diabase sills and dykes. There is a strong possibility that the Coleman sediments in this area are underlain by a Nipissing sill. The youngest known consolidated rocks in the area are kimberlite rocks.

## **EXPLORATION HISTORY**

Extensive work has been carried out in the general Cobalt District but very little has been reported in the immediate area of the Hound Chutes claims. One drill hole was completed by E. Forbear in 1955 at a point approximately 75 m north west of the area.

In December 1998, High-Sense Geophysics Limited carried out an airborne electromagnetic survey over the area on behalf of Branchwater Resources Ltd. Seymour Sears carried out geological mapping in 2003 on behalf of Cabo Mining Corp.

During the summer months of 2009, Alan Kon performed a KIM survey and prospecting over parts of the claims on behalf of Diamond Exploration Inc.

A ground Magnetometer/VLF survey carried out between January 28 and February 4, 2011 by Larder Geophysics of Larder Lake Ontario and Alan Kon who did the initial consultation, ground inspection and organized the work.

Al Kon performed a Phase 1 exploration program in the early summer of 2012 and staked more ground to the east and south of the claims.

## **Work Program**

This program along with the prior exploration program was based on the 2011 geophysical survey performed by Larder Lake Geophysical. The main objective of the earlier program was to determine what the cause of a low Mag anomaly was.

The summer/fall program was to uncover more of the odd looking mafic dike structure and its extent along with prospecting the larger anomaly to the south and smaller anomalies on the claims.

The program started with prospecting and trying to determine the depth of the overburden on the anomalies. A post hole hand auger and mining pick was used to dig but proved inadequate because of the amount of gravel and boulders after 2 to 3 feet of sand.

The excavator was brought in on October 9th for 2 days. It was hoped that after the excavator uncovered extent of the first anomaly it could move to the larger anomaly but because of the unexpected amount of overburden such as sand, gravel and boulders, the budget would not allow it.

Al Kon and two helpers cleaned the stripped area using picks, shovels and brooms to start with because of the absence of water. After a major down pour a high volume/pressure water pump and fire hose was brought in to clean the stripped area.

## **Sampling**

Prior to the stripping, 3 channel samples were taken from below the mafic dyke on or near the contact between the mafic dike and the Huronian conglomerates. A large alteration halo up to 1.5m is clearly visible. Within the altered conglomerates are small brecciated calcite veins with green malachite staining.

After the stripping, washing and mapping 6 more channel and 3 chip samples were taken from the conglomerates on the east side of the mafic dyke. See *Table below*.

<b>Sample Number</b>	<b>Type</b>	<b>Coordinates</b>	<b>Elevation</b>	<b>Date</b>
HCP-01CS	35CM CUT	17 T 599397 5239085	295 m	19/07/2012 10:54
HCP-02CS	60CM CUT	17 T 599408 5239089	293 m	19/07/2012 11:40
HCP -03CS	40CM CUT	17 T 599398 5239079	294 m	19/07/2012 1:42
HCP -04	CHIP	17 T 599400 5239074	293 m	03/10/2012 12:51
HCP -05	CHIP	17 T 599403 5239086	304 m	03/10/2012 2:17
HCP -06	CHIP	17 T 599427 5239063	304 m	16/10/2012 12:56
HCP-07CS	40CM CUT	17 T 599428 5239063	302 m	23/10/2012 11:00
HCP-08CS	70CM CUT	17 T 599423 5239077	303 m	23/10/2012 11:42
HCP-09CS	60CM CUT	17 T 599410 5239083	300 m	23/10/2012 11:58
HCP-10CS	50CM CUT	17 T 599405 5239093	301 m	23/10/2012 12:43
HCP-11CS	50CM CUT	17 T 599408 5239090	300 m	23/10/2012 12:56
HCP-12CS	45CM CUT	17 T 599409 5239092	297 m	23/10/2012 1:20

## Daily Log - Phase 2 - Summer/Fall 2012

July 18 - Property visit, plot GPS points, maps and data.

July 19 - Prospect claim 4243947 & 1140510, cut 3 channel samples on 3007492.

Aug 6 - Prospect claim 114510

Aug 7 - Update AutoCAD map/GPS, GPS points, review data

Aug 8 - Prospect claims 4243947 & 1140510, outline anomaly

Aug 9 - Prospect claim 1140510, update maps

Aug 13 - Overburden depth testing (hand auger), update maps

Oct 3 - Prospect claim 4243947, 3 samples taken

Oct 5 - Prospect claims 4243947, 114510, excavator access

Oct 09 - Supervise excavator on claims 4243947, 114510

Oct 10 - Supervise excavator, prospect stripped area

Oct 11 - Clean stripped outcrop

Oct 16 - Clean and sample stripped outcrop, 1 sample taken

Oct 17 - Stripped outcrop washing

Oct 18 - Hi-pressure OC washing

Oct 19 - Hi-pressure OC washing

Oct 22 - Hi-pressure OC Washing, Mapping, and Channel Sampling

Oct 23 - Channel Sampling - 6 sample taken

Oct 30 - Ship samples

## Pictures





## **Recommendations**

Even though a considerable amount of work was performed on the Hound Chutes Rd claims, more ground work is required.

When the funds are available a more detailed exploration program should be done on the claims starting with a cut grid and followed by prospecting, sampling and mapping. There are several more anomalies on the claims and all should be looked at more thoroughly.

The big anomaly south of the stripped area should be the next target for surface stripping followed by the hi-mag anomaly to the south west.

If possible a diamond drilling program should also be considered.

## **Special Note:**

This report is on the physical work performed on the Hound Chutes claims only. A detailed geological report will follow a later date.

Thank you.

Respectfully submitted by:



Alan Kon

## **APPENDIX I**

**CLIENT NAME:** ADK EXPLORATION  
PO BOX 1375  
HAILEYBURY, ON P0J1K0  
(705) 648-9680

**ATTENTION TO:** ALAN KON

**PROJECT NO:** HOUND CHUTES PROPERTY

**AGAT WORK ORDER:** 12U657613

**SOLID ANALYSIS REVIEWED BY:** Yufei Chen, Analyst

**DATE REPORTED:** Nov 13, 2012

**PAGES (INCLUDING COVER):** 7

Should you require any information regarding this analysis please contact your client services representative at (905) 501-9998

**\*NOTES**

All samples are stored at no charge for 90 days. Please contact the lab if you require additional sample storage time.



**AGAT** Laboratories

## Certificate of Analysis

AGAT WORK ORDER: 12U657613

PROJECT NO.: HOUND CHUTES PROPERTY

ATTENTION TO: ALAN KON

5623 McDADAM ROAD  
MISSISSAUGA, ONTARIO  
CANADA L4Z 1N9  
TEL (905)501-0998  
FAX (905)501-0589  
<http://www.agatlabs.com>

CLIENT NAME: ADK EXPLORATION

### Aqua Regia Digest - Metals Package, ICP-OES finish (201073)

Sample Description	Analyte: RDL:	DATE RECEIVED: Oct 26, 2012												DATE REPORTED: Nov 13, 2012												SAMPLE TYPE: Rock											
		Sample Weight kg	Ag	Al	As	B	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cu	Ge	Ga	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Ni	P	Pb								
HCP-01	0.01	1.52	<0.2	1.01	9	<5	114	<0.5	<1	0.14	<0.5	30	13.5	119	35.2																						
HCP-02		1.84	<0.2	2.89	4	8	456	1.8	<1	2.34	<0.5	29	12.8	102	39.7																						
HCP-03		1.46	<0.2	1.04	2	14	80	0.6	<1	9.07	0.6	44	7.1	55.9	165																						
HCP-04		0.76	<0.2	0.97	3	5	29	<0.5	<1	10.7	0.6	62	10.5	68.0	42.5																						
HCP-05		2.86	<0.2	1.67	<1	27	2340	4.9	<1	7.49	1.8	<1	53.5	201	236																						
HCP-06		1.26	<0.2	4.23	<1	9	579	1.7	<1	3.25	0.6	27	11.8	79.3	73.2																						
HCP-07		1.06	<0.2	3.48	<1	7	797	2.5	<1	0.86	0.8	23	23.7	122	114																						
HCP-08		1.18	<0.2	2.34	<1	6	306	1.3	<1	0.97	<0.5	32	12.6	80.6	38.2																						
HCP-09		1.12	<0.2	1.80	<1	9	277	1.4	<1	1.52	0.8	31	16.6	111	41.5																						
HCP-10		1.72	<0.2	2.66	<1	9	298	2.2	<1	1.25	0.9	36	14.9	113	36.6																						
HCP-11		1.16	<0.2	3.18	<1	11	1510	3.5	<1	2.00	1.2	35	31.2	155	291																						
HCP-12		0.84	<0.2	3.44	<1	7	443	2.1	<1	1.23	0.8	30	13.9	93.1	54.4																						
	Analyte: Unit: RDL:	Fe	Ga	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Ni	P	Pb																						
		0.01	5	1	1	0.01	1	1	0.01	1	0.01	1	0.01	10	0.5																						
HCP-01		2.71	8	<1	3	0.05	14	18	1.09	449	0.5	0.05	414	520	<0.5																						
HCP-02		3.04	12	<1	2	0.87	14	26	1.95	646	3.1	1.73	46.3	1290	4.1																						
HCP-03		1.94	7	<1	1	0.33	19	122	5.76	502	1.3	0.08	31.5	802	1.8																						
HCP-04		1.98	8	<1	2	0.04	33	16	1.00	816	<0.5	0.03	31.1	307	<0.5																						
HCP-05		6.70	14	<1	10	1.07	2	15	11.5	1550	<0.5	0.07	440	8010	9.8																						
HCP-06		2.74	13	<1	<1	0.67	14	24	1.80	602	2.4	3.34	41.4	2470	3.2																						
HCP-07		3.87	13	<1	5	0.71	13	26	3.43	891	1.1	1.76	140	2090	3.7																						
HCP-08		2.66	12	<1	<1	0.65	17	18	1.85	526	0.8	0.99	41.7	34	1.4																						
HCP-09		3.53	13	<1	4	0.99	15	28	2.27	823	1.2	0.16	52.2	452	2.0																						
HCP-10		3.49	12	<1	4	0.69	19	31	3.04	674	0.9	0.71	50.7	558	1.2																						
HCP-11		5.11	15	1	4	0.83	24	27	4.63	1140	1.4	0.96	178	5110	7.0																						
HCP-12		3.32	12	3	0.60	17	24	2.03	569	1.1	1.68	512	882	3.0																							

Certified By: J. Doe.



## Certificate of Analysis

AGAT WORK ORDER: 12U657613

PROJECT NO: HANR CHITES B1

PROJECT NO: HUND CHOIES PROPERTY

5623 MCGADAM ROAD  
MISSISSAUGA, ONTARIO  
CANADA L4Z 1N9  
TEL (905)501-9998  
FAX (905)501-0589  
<http://www.agatlabs.com>

CLIENT NAME: ADR EXPLORATION

Aqua Regia Digest - Metals Package, ICP-OES finish (201073)

## AGAT CERTIFICATE OF ANALYSIS (V1)

*Results relate only to the items tested and to all the items tested*

*Certified By:*



**AGAT**

Laboratories

5623 McADAM ROAD  
MISSISSAUGA, ONTARIO  
CANADA L4Z 1N9  
TEL (905)501-9998  
FAX (905)501-0589  
<http://www.agatlabs.com>

## Quality Assurance

CLIENT NAME: ADK EXPLORATION

PROJECT NO: HOUND CHUTES PROPERTY

AGAT WORK ORDER: 12U657613

ATTENTION TO: ALAN KON

### Solid Analysis

RPT Date: Nov 13, 2012		REPLICATE			Method Blank	REFERENCE MATERIAL					
PARAMETER	Batch	Sample Id	Original	Rep #1	RPD		Result Value	Expect Value	Recovery	Acceptable Limits	
										Lower	Upper
<b>Aqua Regia Digest - Metals Package, ICP-OES finish (201073)</b>											
Ag	1	3871933	< 0.2	< 0.2	0.0%	< 0.2	14.0	13.0	108%	80%	120%
Al	1	3871933	1.01	1.11	9.4%	< 0.01				80%	120%
As	1	3871933	9	7	25.0%	< 1				80%	120%
B	1	3871933	< 5	< 5	0.0%	< 5				80%	120%
Ba	1	3871933	114	124	8.4%	< 1				80%	120%
Be	1	3871933	< 0.5	< 0.5	0.0%	< 0.5				80%	120%
Bi	1	3871933	< 1	< 1	0.0%	< 1				80%	120%
Ca	1	3871933	0.14	0.15	6.9%	< 0.01				80%	120%
Cd	1	3871933	< 0.5	< 0.5	0.0%	< 0.5				80%	120%
Ce	1	3871933	30	33	9.5%	< 1				80%	120%
Co	1	3871933	13.5	14.6	7.8%	< 0.5				80%	120%
Cr	1	3871933	119	133	11.1%	< 0.5				80%	120%
Cu	1	3871933	35.2	35.2	0.0%	< 0.5	5714	6000	95%	80%	120%
Fe	1	3871933	2.71	3.04	11.5%	< 0.01				80%	120%
Ga	1	3871933	8	9	11.8%	< 5				80%	120%
Hg	1	3871933	< 1	< 1	0.0%	< 1				80%	120%
In	1	3871933	3	2		< 1				80%	120%
K	1	3871933	0.051	0.061	17.9%	< 0.01				80%	120%
La	1	3871933	14	16	13.3%	< 1				80%	120%
Li	1	3871933	18	20	10.5%	< 1				80%	120%
Mg	1	3871933	1.09	1.19	8.8%	< 0.01				80%	120%
Mn	1	3871933	449	520	14.7%	< 1				80%	120%
Mo	1	3871933	0.5	< 0.5		< 0.5	359	360	99%	80%	120%
Na	1	3871933	0.05	0.06	18.2%	< 0.01				80%	120%
Ni	1	3871933	41.4	46.6	11.8%	< 0.5				80%	120%
P	1	3871933	520	578	10.6%	< 10	660	600	110%	80%	120%
Pb	1	3871933	< 0.5	< 0.5	0.0%	< 0.5				80%	120%
Rb	1	3871933	< 10	< 10	0.0%	< 10				80%	120%
S	1	3871933	0.0474	0.0510	7.3%	< 0.005				80%	120%
Sb	1	3871933	< 1	1		< 1				80%	120%
Sc	1	3871933	6.28	7.07	11.8%	< 0.5				80%	120%
Se	1	3871933	< 10	< 10	0.0%	< 10				80%	120%
Sn	1	3871933	< 5	< 5	0.0%	< 5				80%	120%
Sr	1	3871933	15.5	17.7	13.3%	< 0.5				80%	120%
Ta	1	3871933	< 10	< 10	0.0%	< 10				80%	120%
Te	1	3871933	< 10	< 10	0.0%	< 10				80%	120%
Th	1	3871933	< 5	< 5	0.0%	< 5				80%	120%
Ti	1	3871933	0.024	0.028	15.4%	< 0.01				80%	120%
Tl	1	3871933	< 5	< 5	0.0%	< 5				80%	120%
U	1	3871933	< 5	< 5	0.0%	< 5				80%	120%
V	1	3871933	69.5	78.1	11.7%	< 0.5				80%	120%
W	1	3871933	< 1	< 1	0.0%	< 1				80%	120%
Y	1	3871933	6	7	15.4%	< 1	6	7	81%	80%	120%
Zn	1	3871933	49.6	53.7	7.9%	< 0.5				80%	120%



## Quality Assurance

CLIENT NAME: ADK EXPLORATION

PROJECT NO: HOUND CHUTES PROPERTY

AGAT WORK ORDER: 12U657613

ATTENTION TO: ALAN KON

### Solid Analysis (Continued)

RPT Date: Nov 13, 2012		REPLICATE			Method Blank	REFERENCE MATERIAL				
PARAMETER	Batch	Sample Id	Original	Rep #1	RPD		Result Value	Expect Value	Recovery	Acceptable Limits
							Lower	Upper		
Zr	1	3871933	17	20	16.2%	< 5			80%	120%
<b>Aqua Regia Digest - Metals Package, ICP-OES finish (201073)</b>										
Ag	1	3871944	< 0.2	< 0.2	0.0%	< 0.2			80%	120%
Al	1	3871944	3.44	3.48	1.2%	< 0.01			80%	120%
As	1	3871944	< 1	< 1	0.0%	< 1			80%	120%
B	1	3871944	7	6	15.4%	< 5			80%	120%
Ba	1	3871944	443	442	0.2%	< 1			80%	120%
Be	1	3871944	2.14	2.17	1.4%	< 0.5			80%	120%
Bi	1	3871944	< 1	< 1	0.0%	< 1			80%	120%
Ca	1	3871944	1.23	1.22	0.8%	< 0.01			80%	120%
Cd	1	3871944	0.83	0.74	11.5%	< 0.5			80%	120%
Ce	1	3871944	30	30	0.0%	< 1			80%	120%
Co	1	3871944	13.9	14.1	1.4%	< 0.5			80%	120%
Cr	1	3871944	93.1	94.9	1.9%	< 0.5			80%	120%
Cu	1	3871944	54.4	55.2	1.5%	< 0.5			80%	120%
Fe	1	3871944	3.32	3.31	0.3%	< 0.01			80%	120%
Ga	1	3871944	12	13	8.0%	< 5			80%	120%
Hg	1	3871944	< 1	< 1	0.0%	< 1			80%	120%
In	1	3871944	3	5		< 1			80%	120%
K	1	3871944	0.60	0.60	0.0%	< 0.01			80%	120%
La	1	3871944	17	18	5.7%	< 1			80%	120%
Li	1	3871944	24	24	0.0%	< 1			80%	120%
Mg	1	3871944	2.03	2.04	0.5%	< 0.01			80%	120%
Mn	1	3871944	569	592	4.0%	< 1			80%	120%
Mo	1	3871944	1.06	0.90	16.3%	< 0.5			80%	120%
Na	1	3871944	1.68	1.71	1.8%	< 0.01			80%	120%
Ni	1	3871944	51.2	52.1	1.7%	< 0.5			80%	120%
P	1	3871944	882	887	0.6%	< 10			80%	120%
Pb	1	3871944	3.00	2.94	2.0%	< 0.5			80%	120%
Rb	1	3871944	164	166	1.2%	< 10			80%	120%
S	1	3871944	0.0092	0.0100	8.3%	< 0.005			80%	120%
Sb	1	3871944	< 1	< 1	0.0%	< 1			80%	120%
Sc	1	3871944	9.7	9.8	1.0%	< 0.5			80%	120%
Se	1	3871944	< 10	< 10	0.0%	< 10			80%	120%
Sn	1	3871944	< 5	< 5	0.0%	< 5			80%	120%
Sr	1	3871944	141	145	2.8%	< 0.5			80%	120%
Ta	1	3871944	< 10	< 10	0.0%	< 10			80%	120%
Te	1	3871944	< 10	< 10	0.0%	< 10			80%	120%
Th	1	3871944	< 5	< 5	0.0%	< 5			80%	120%
Ti	1	3871944	0.18	0.18	0.0%	< 0.01			80%	120%
Tl	1	3871944	< 5	< 5	0.0%	< 5			80%	120%
U	1	3871944	< 5	< 5	0.0%	< 5			80%	120%
V	1	3871944	80.6	81.9	1.6%	< 0.5			80%	120%
W	1	3871944	< 1	< 1	0.0%	< 1			80%	120%



Laboratories

5623 McADAM ROAD  
MISSISSAUGA, ONTARIO  
CANADA L4Z 1N9  
TEL (905)501-9998  
FAX (905)501-0589  
<http://www.agatlabs.com>

## Quality Assurance

CLIENT NAME: ADK EXPLORATION  
PROJECT NO: HOUND CHUTES PROPERTY

AGAT WORK ORDER: 12U657613  
ATTENTION TO: ALAN KON

### Solid Analysis (Continued)

RPT Date: Nov 13, 2012		REPLICATE				Method Blank	REFERENCE MATERIAL					
PARAMETER	Batch	Sample Id	Original	Rep #1	RPD		Result Value	Expect Value	Recovery	Acceptable Limits		
										Lower	Upper	
Y	1	3871944	10	10	0.0%	< 1				80%	120%	
Zn	1	3871944	52.7	53.9	2.3%	< 0.5				80%	120%	
Zr	1	3871944	14	14	0.0%	< 5				80%	120%	

Certified By:

## Method Summary

CLIENT NAME: ADK EXPLORATION


AGAT WORK ORDER: 12U657613

PROJECT NO: HOUND CHUTES PROPERTY

ATTENTION TO: ALAN KON

PARAMETER	AGAT S.O.P	LITERATURE REFERENCE	ANALYTICAL TECHNIQUE
<b>Solid Analysis</b>			
Sample Login Weight	MIN-12009		BALANCE
Ag	MIN-200-12020		ICP/OES
Al	MIN-200-12020		ICP/OES
As	MIN-200-12020		ICP/OES
B	MIN-200-12020		ICP/OES
Ba	MIN-200-12020		ICP/OES
Be	MIN-200-12020		ICP/OES
Bi	MIN-200-12020		ICP/OES
Ca	MIN-200-12020		ICP/OES
Cd	MIN-200-12020		ICP/OES
Ce	MIN-200-12020		ICP/OES
Co	MIN-200-12020		ICP/OES
Cr	MIN-200-12020		ICP/OES
Cu	MIN-200-12020		ICP/OES
Fe	MIN-200-12020		ICP/OES
Ga	MIN-200-12020		ICP/OES
Hg	MIN-200-12020		ICP/OES
In	MIN-200-12020		ICP/OES
K	MIN-200-12020		ICP/OES
La	MIN-200-12020		ICP/OES
Li	MIN-200-12020		ICP/OES
Mg	MIN-200-12020		ICP/OES
Mn	MIN-200-12020		ICP/OES
Mo	MIN-200-12020		ICP/OES
Na	MIN-200-12020		ICP/OES
Ni	MIN-200-12020		ICP/OES
P	MIN-200-12020		ICP/OES
Pb	MIN-200-12020		ICP/OES
Rb	MIN-200-12020		ICP/OES
S	MIN-200-12020		ICP/OES
Sb	MIN-200-12020		ICP/OES
Sc	MIN-200-12020		ICP/OES
Se	MIN-200-12020		ICP/OES
Sn	MIN-200-12020		ICP/OES
Sr	MIN-200-12020		ICP/OES
Ta	MIN-200-12020		ICP/OES
Te	MIN-200-12020		ICP/OES
Th	MIN-200-12020		ICP/OES
Ti	MIN-200-12020		ICP/OES
Tl	MIN-200-12020		ICP/OES
U	MIN-200-12020		ICP/OES
V	MIN-200-12020		ICP/OES
W	MIN-200-12020		ICP/OES
Y	MIN-200-12020		ICP/OES
Zn	MIN-200-12020		ICP/OES
Zr	MIN-200-12020		ICP/OES

## **APPENDIX II**



1cm = 2m

Bush

- NOTES:
- \* mafic Dike  
Strike =  $142^\circ$   
Dip =  $90^\circ$   
Elav = 313m
  - \* Conglomerate  
1.5 m Alteration halo on contact malachite staining

