

Friday, February 17, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/01/2012
 Date Completed: 02/15/2012
 Job #: 201240230
 Reference: TL 12 230
 Sample #: 211

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
21298	1212429	42	0.001	0.042
21299	1212430	1151	0.034	1.151
21300	1212431	63	0.002	0.063
21301	1212432	48	0.001	0.048
21302	1212433	19	<0.001	0.019
21303	1212434	88	0.003	0.088
21304	1212435	228	0.007	0.228
21305	1212436	367	0.011	0.367
21306	1212437	449	0.013	0.449
21307	1212438	55	0.002	0.055
21308 Dup	1212438	76	0.002	0.076
21309	1212439	38	0.001	0.038
21310	1212440	7	<0.001	0.007
21311	1212441	29	<0.001	0.029
21312	1212442	101	0.003	0.101
21313	1212443	436	0.013	0.436
21314	1212444	1071	0.031	1.071
21315	1212445	128	0.004	0.128
21316	1212446	40	0.001	0.040
21317	1212447	242	0.007	0.242
21318	1212448	2148	0.063	2.148
21319 Dup	1212448	2393	0.070	2.393
21320	1212449	60	0.002	0.060
21321	1212450	265	0.008	0.265
21322	1212451	19	<0.001	0.019
21323	1212452	14	<0.001	0.014
21324	1212453	5	<0.001	0.005
21325	1212454	12	<0.001	0.012
21326	1212455	14	<0.001	0.014
21327	1212456	16	<0.001	0.016

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Friday, February 17, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/01/2012
 Date Completed: 02/15/2012
 Job #: 201240230
 Reference: TL 12 230
 Sample #: 211

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
21328	1212457	6	<0.001	0.006
21329	1212458	31	<0.001	0.031
21330 Dup	1212458	40	0.001	0.040
21331	1212459	77	0.002	0.077
21332	1212460	6	<0.001	0.006
21333	1212461	373	0.011	0.373
21334	1212462	21	<0.001	0.021
21335	1212463	12	<0.001	0.012
21336	1212464	12	<0.001	0.012
21337	1212465	28	<0.001	0.028
21338	1212466	35	0.001	0.035
21339	1212467	14	<0.001	0.014
21340	1212468	14	<0.001	0.014
21341 Dup	1212468	15	<0.001	0.015
21342	1212469	266	0.008	0.266
21343	1212470	5325	0.155	5.325
21344	1212471	29	<0.001	0.029
21345	1212472	12	<0.001	0.012
21346	1212473	11	<0.001	0.011
21347	1212474	16	<0.001	0.016
21348	1212475	16	<0.001	0.016
21349	1212476	20	<0.001	0.020
21350	1212477	26	<0.001	0.026
21351	1212478	25	<0.001	0.025
21352 Dup	1212478	23	<0.001	0.023
21353	1212479	242	0.007	0.242
21354	1212480	9	<0.001	0.009
21355	1212481	80	0.002	0.080
21356	1212482	226	0.007	0.226
21357	1212483	98	0.003	0.098

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Friday, February 17, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/01/2012
 Date Completed: 02/15/2012
 Job #: 201240230
 Reference: TL 12 230
 Sample #: 211

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
21358	1212484	169	0.005	0.169
21359	1212485	100	0.003	0.100
21360	1212486	129	0.004	0.129
21361	1212487	5626	0.164	5.626
21362	1212488	379	0.011	0.379
21363 Rep	1212488	368	0.011	0.368
21364	1212489	2387	0.070	2.387
21365	1212490	1457	0.042	1.457
21366	1212491	318	0.009	0.318
21367	1212492	154	0.004	0.154
21368	1212493	147	0.004	0.147
21369	1212494	221	0.006	0.221
21370	1212495	417	0.012	0.417
21371	1212496	167	0.005	0.167
21372	1212497	80	0.002	0.080
21373	1212498	153	0.004	0.153
21374 Dup	1212498	149	0.004	0.149
21375	1212499	138	0.004	0.138
21376	1212500	7	<0.001	0.007
21377	1212501	158	0.005	0.158
21378	1212502	376	0.011	0.376
21379	1212503	48	0.001	0.048
21380	1212504	55	0.002	0.055
21381	1212505	93	0.003	0.093
21382	1212506	127	0.004	0.127
21383	1212507	80	0.002	0.080
21384	1212508	44	0.001	0.044
21385 Dup	1212508	42	0.001	0.042
21386	1212509	196	0.006	0.196
21387	1212510	267	0.008	0.267

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Friday, February 17, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/01/2012
 Date Completed: 02/15/2012
 Job #: 201240230
 Reference: TL 12 230
 Sample #: 211

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
21388	1212511	38	0.001	0.038
21389	1212512	62	0.002	0.062
21390	1212513	18	<0.001	0.018
21391	1212514	21	<0.001	0.021
21392	1212515	59	0.002	0.059
21393	1212516	44	0.001	0.044
21394	1212517	94	0.003	0.094
21395	1212518	24	<0.001	0.024
21396 Dup	1212518	20	<0.001	0.020
21397	1212519	22	<0.001	0.022
21398	1212520	5	<0.001	0.005
21399	1212521	28	<0.001	0.028
21400	1212522	40	0.001	0.040
21401	1212523	423	0.012	0.423
21402	1212524	117	0.003	0.117
21403	1212525	115	0.003	0.115
21404	1212526	20	<0.001	0.020
21405	1212527	25	<0.001	0.025
21406	1212528	46	0.001	0.046
21407 Dup	1212528	73	0.002	0.073
21408	1212529	937	0.027	0.937
21409	1212530	5070	0.148	5.070
21410	1212531	26	<0.001	0.026
21411	1212532	18	<0.001	0.018
21412	1212533	23	<0.001	0.023
21413	1212534	39	0.001	0.039
21414	1212535	41	0.001	0.041
21415	1212536	26	<0.001	0.026
21416	1212537	19	<0.001	0.019
21417	1212538	40	0.001	0.040

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Friday, February 17, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/01/2012
 Date Completed: 02/15/2012
 Job #: 201240230
 Reference: TL 12 230
 Sample #: 211

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
21418 Dup	1212538	45	0.001	0.045
21419	1212539	15	<0.001	0.015
21420	1212540	8	<0.001	0.008
21421	1212541	24	<0.001	0.024
21422	1212542	26	<0.001	0.026
21423	1212543	30	<0.001	0.030
21424	1212544	34	<0.001	0.034
21425	1212545	149	0.004	0.149
21426	1212546	10057	0.293	10.057
21427	1212547	59	0.002	0.059
21428	1212548	14	<0.001	0.014
21429 Rep	1212548	14	<0.001	0.014
21430	1212549	21	<0.001	0.021
21431	1212550	1135	0.033	1.135
21432	1212551	114	0.003	0.114
21433	1212552	35	0.001	0.035
21434	1212553	30	<0.001	0.030
21435	1212554	27	<0.001	0.027
21436	1212555	13	<0.001	0.013
21437	1212556	21	<0.001	0.021
21438	1212557	20	<0.001	0.020
21439	1212558	122	0.004	0.122
21440 Dup	1212558	94	0.003	0.094
21441	1212559	26	<0.001	0.026
21442	1212560	<5	<0.001	<0.005
21443	1212561	30	<0.001	0.030
21444	1212562	6	<0.001	0.006
21445	1212563	11	<0.001	0.011
21446	1212564	85	0.002	0.085
21447	1212565	18	<0.001	0.018

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Friday, February 17, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/01/2012
 Date Completed: 02/15/2012
 Job #: 201240230
 Reference: TL 12 230
 Sample #: 211

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
21448	1212566	23	<0.001	0.023
21449	1212567	21	<0.001	0.021
21450	1212568	31	<0.001	0.031
21451 Dup	1212568	24	<0.001	0.024
21452	1212569	5	<0.001	0.005
21453	1212570	274	0.008	0.274
21454	1212571	11	<0.001	0.011
21455	1212572	10	<0.001	0.010
21456	1212573	20	<0.001	0.020
21457	1212574	<5	<0.001	<0.005
21458	1212575	6	<0.001	0.006
21459	1212576	39	0.001	0.039
21460	1212577	95	0.003	0.095
21461	1212578	175	0.005	0.175
21462 Dup	1212578	203	0.006	0.203
21463	1212579	315	0.009	0.315
21464	1212580	9	<0.001	0.009
21465	1212581	23	<0.001	0.023
21466	1212582	30	<0.001	0.030
21467	1212583	9606	0.280	9.606
21468	1212584	217	0.006	0.217
21469	1212585	498	0.015	0.498
21470	1212586	245	0.007	0.245
21471	1212587	202	0.006	0.202
21472	1212588	31	<0.001	0.031
21473 Dup	1212588	29	<0.001	0.029
21474	1212589	5	<0.001	0.005
21475	1212590	4948	0.144	4.948
21476	1212591	34	<0.001	0.034
21477	1212592	6	<0.001	0.006

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Friday, February 17, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/01/2012
 Date Completed: 02/15/2012
 Job #: 201240230
 Reference: TL 12 230
 Sample #: 211

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
21478	1212593	72	0.002	0.072
21479	1212594	146	0.004	0.146
21480	1212595	68	0.002	0.068
21481	1212596	54	0.002	0.054
21482	1212597	40	0.001	0.040
21483	1212598	<5	<0.001	<0.005
21484 Dup	1212598	9	<0.001	0.009
21485	1212599	<5	<0.001	<0.005
21486	1212600	6	<0.001	0.006
21487	1212601	15	<0.001	0.015
21488	1212602	<5	<0.001	<0.005
21489	1212603	<5	<0.001	<0.005
21490	1212604	9	<0.001	0.009
21491	1212605	<5	<0.001	<0.005
21492	1212606	13	<0.001	0.013
21493	1212607	12	<0.001	0.012
21494	1212608	91	0.003	0.091
21495 Rep	1212608	18	<0.001	0.018
21496	1212609	<5	<0.001	<0.005
21497	1212610	1403	0.041	1.403
21498	1212611	96	0.003	0.096
21499	1212612	<5	<0.001	<0.005
21500	1212613	6	<0.001	0.006
21501	1212614	9	<0.001	0.009
21502	1212615	6	<0.001	0.006
21503	1212616	<5	<0.001	<0.005
21504	1212617	<5	<0.001	<0.005
21505	1212618	<5	<0.001	<0.005
21506 Dup	1212618	6	<0.001	0.006
21507	1212619	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Friday, February 17, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/01/2012
 Date Completed: 02/15/2012
 Job #: 201240230
 Reference: TL 12 230
 Sample #: 211

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
21508	1212620	5	<0.001	0.005
21509	1212621	<5	<0.001	<0.005
21510	1212622	<5	<0.001	<0.005
21511	1212623	8	<0.001	0.008
21512	1212624	<5	<0.001	<0.005
21513	1212625	<5	<0.001	<0.005
21514	1212626	<5	<0.001	<0.005
21515	1212627	<5	<0.001	<0.005
21516	1212628	13	<0.001	0.013
21517 Dup	1212628	14	<0.001	0.014
21518	1212629	<5	<0.001	<0.005
21519	1212630	269	0.008	0.269
21520	1212631	<5	<0.001	<0.005
21521	1212632	6	<0.001	0.006
21522	1212633	<5	<0.001	<0.005
21523	1212634	<5	<0.001	<0.005
21524	1212635	<5	<0.001	<0.005
21525	1212636	<5	<0.001	<0.005
21526	1212637	<5	<0.001	<0.005
21527	1212638	<5	<0.001	<0.005
21528 Dup	1212638	<5	<0.001	<0.005
21529	1212639	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Friday, February 24, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/10/2012
 Date Completed: 02/24/2012
 Job #: 201240294
 Reference: TL12231
 Sample #: 309

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
28160	1212640	<5	<0.001	<0.005
28161	1212641	11	<0.001	0.011
28162	1212642	6	<0.001	0.006
28163	1212643	37	0.001	0.037
28164	1212644	<5	<0.001	<0.005
28165	1212645	8	<0.001	0.008
28166	1212646	<5	<0.001	<0.005
28167	1212647	<5	<0.001	<0.005
28168	1212648	<5	<0.001	<0.005
28169	1212649	<5	<0.001	<0.005
28170 Dup	1212649	6	<0.001	0.006
28171	1212650	4957	0.145	4.957
28172	1212651	<5	<0.001	<0.005
28173	1212652	5	<0.001	0.005
28174	1212653	<5	<0.001	<0.005
28175	1212654	6	<0.001	0.006
28176	1212655	<5	<0.001	<0.005
28177	1212656	<5	<0.001	<0.005
28178	1212657	<5	<0.001	<0.005
28179	1212658	<5	<0.001	<0.005
28180	1212659	<5	<0.001	<0.005
28181 Dup	1212659	<5	<0.001	<0.005
28182	1212660	5	<0.001	0.005
28183	1212661	<5	<0.001	<0.005
28184	1212662	<5	<0.001	<0.005
28185	1212663	<5	<0.001	<0.005
28186	1212664	9	<0.001	0.009
28187	1212665	<5	<0.001	<0.005
28188	1212666	<5	<0.001	<0.005
28189	1212667	7	<0.001	0.007

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Friday, February 24, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/10/2012
 Date Completed: 02/24/2012
 Job #: 201240294
 Reference: TL12231
 Sample #: 309

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
28190	1212668	6	<0.001	0.006
28191	1212669	6	<0.001	0.006
28192 Dup	1212669	7	<0.001	0.007
28193	1212670	1183	0.035	1.183
28194	1212671	9	<0.001	0.009
28195	1212672	7	<0.001	0.007
28196	1212673	<5	<0.001	<0.005
28197	1212674	<5	<0.001	<0.005
28198	1212675	<5	<0.001	<0.005
28199	1212676	6	<0.001	0.006
28200	1212677	<5	<0.001	<0.005
28201	1212678	<5	<0.001	<0.005
28202	1212679	<5	<0.001	<0.005
28203 Dup	1212679	<5	<0.001	<0.005
28204	1212680	6	<0.001	0.006
28205	1212681	<5	<0.001	<0.005
28206	1212682	<5	<0.001	<0.005
28207	1212683	<5	<0.001	<0.005
28208	1212684	6	<0.001	0.006
28209	1212685	<5	<0.001	<0.005
28210	1212686	5	<0.001	0.005
28211	1212687	<5	<0.001	<0.005
28212	1212688	6	<0.001	0.006
28213	1212689	<5	<0.001	<0.005
28214 Dup	1212689	<5	<0.001	<0.005
28215	1212690	255	0.007	0.255
28216	1212691	7	<0.001	0.007
28217	1212692	6	<0.001	0.006
28218	1212693	<5	<0.001	<0.005
28219	1212694	6	<0.001	0.006

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Friday, February 24, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/10/2012
 Date Completed: 02/24/2012
 Job #: 201240294
 Reference: TL12231
 Sample #: 309

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
28220	1212695	<5	<0.001	<0.005
28221	1212696	<5	<0.001	<0.005
28222	1212697	6	<0.001	0.006
28223	1212698	5	<0.001	0.005
28224	1212699	5	<0.001	0.005
28225 Rep	1212699	<5	<0.001	<0.005
28226	1212700	6	<0.001	0.006
28227	1212701	<5	<0.001	<0.005
28228	1212702	6	<0.001	0.006
28229	1212703	5	<0.001	0.005
28230	1212704	5	<0.001	0.005
28231	1212705	6	<0.001	0.006
28232	1212706	6	<0.001	0.006
28233	1212707	<5	<0.001	<0.005
28234	1212708	<5	<0.001	<0.005
28235	1212709	<5	<0.001	<0.005
28236 Dup	1212709	<5	<0.001	<0.005
28237	1212710	4822	0.141	4.822
28238	1212711	<5	<0.001	<0.005
28239	1212712	<5	<0.001	<0.005
28240	1212713	<5	<0.001	<0.005
28241	1212714	<5	<0.001	<0.005
28242	1212715	<5	<0.001	<0.005
28243	1212716	<5	<0.001	<0.005
28244	1212717	<5	<0.001	<0.005
28245	1212718	<5	<0.001	<0.005
28246	1212719	<5	<0.001	<0.005
28247 Dup	1212719	<5	<0.001	<0.005
28248	1212720	<5	<0.001	<0.005
28249	1212721	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Friday, February 24, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/10/2012
 Date Completed: 02/24/2012
 Job #: 201240294
 Reference: TL12231
 Sample #: 309

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
28250	1212722	<5	<0.001	<0.005
28251	1212723	<5	<0.001	<0.005
28252	1212724	<5	<0.001	<0.005
28253	1212725	<5	<0.001	<0.005
28254	1212726	<5	<0.001	<0.005
28255	1212727	<5	<0.001	<0.005
28256	1212728	<5	<0.001	<0.005
28257	1212729	<5	<0.001	<0.005
28258 Dup	1212729	<5	<0.001	<0.005
28259	1212730	1071	0.031	1.071
28260	1212731	10	<0.001	0.010
28261	1212732	7	<0.001	0.007
28262	1212733	<5	<0.001	<0.005
28263	1212734	6	<0.001	0.006
28264	1212735	6	<0.001	0.006
28265	1212736	<5	<0.001	<0.005
28266	1212737	5	<0.001	0.005
28267	1212738	5	<0.001	0.005
28268	1212739	6	<0.001	0.006
28269 Dup	1212739	5	<0.001	0.005
28270	1212740	<5	<0.001	<0.005
28271	1212741	<5	<0.001	<0.005
28272	1212742	<5	<0.001	<0.005
28273	1212743	<5	<0.001	<0.005
28274	1212744	5	<0.001	0.005
28275	1212745	<5	<0.001	<0.005
28276	1212746	<5	<0.001	<0.005
28277	1212747	<5	<0.001	<0.005
28278	1212748	5	<0.001	0.005
28279	1212749	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Friday, February 24, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/10/2012
 Date Completed: 02/24/2012
 Job #: 201240294
 Reference: TL12231
 Sample #: 309

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
28280 Dup	1212749	5	<0.001	0.005
28281	1212750	254	0.007	0.254
28282	1212751	<5	<0.001	<0.005
28283	1212752	<5	<0.001	<0.005
28284	1212753	<5	<0.001	<0.005
28285	1212754	<5	<0.001	<0.005
28286	1212755	<5	<0.001	<0.005
28287	1212756	<5	<0.001	<0.005
28288	1212757	<5	<0.001	<0.005
28289	1212758	<5	<0.001	<0.005
28290	1212759	<5	<0.001	<0.005
28291 Rep	1212759	<5	<0.001	<0.005
28292	1212760	<5	<0.001	<0.005
28293	1212761	10	<0.001	0.010
28294	1212762	<5	<0.001	<0.005
28295	1212763	<5	<0.001	<0.005
28296	1212764	<5	<0.001	<0.005
28297	1212765	<5	<0.001	<0.005
28298	1212766	<5	<0.001	<0.005
28299	1212767	<5	<0.001	<0.005
28300	1212768	<5	<0.001	<0.005
28301	1212769	<5	<0.001	<0.005
28302 Dup	1212769	<5	<0.001	<0.005
28303	1212770	5322	0.155	5.322
28304	1212771	<5	<0.001	<0.005
28305	1212772	<5	<0.001	<0.005
28306	1212773	<5	<0.001	<0.005
28307	1212774	<5	<0.001	<0.005
28308	1212775	<5	<0.001	<0.005
28309	1212776	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Friday, February 24, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/10/2012
 Date Completed: 02/24/2012
 Job #: 201240294
 Reference: TL12231
 Sample #: 309

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
28310	1212777	<5	<0.001	<0.005
28311	1212778	<5	<0.001	<0.005
28312	1212779	<5	<0.001	<0.005
28313 Dup	1212779	<5	<0.001	<0.005
28314	1212780	8	<0.001	0.008
28315	1212781	<5	<0.001	<0.005
28316	1212782	<5	<0.001	<0.005
28317	1212783	<5	<0.001	<0.005
28318	1212784	<5	<0.001	<0.005
28319	1212785	<5	<0.001	<0.005
28320	1212786	<5	<0.001	<0.005
28321	1212787	<5	<0.001	<0.005
28322	1212788	<5	<0.001	<0.005
28323	1212789	<5	<0.001	<0.005
28324 Dup	1212789	<5	<0.001	<0.005
28325	1212790	1186	0.035	1.186
28326	1212791	9	<0.001	0.009
28327	1212792	5	<0.001	0.005
28328	1212793	5	<0.001	0.005
28329	1212794	<5	<0.001	<0.005
28330	1212795	<5	<0.001	<0.005
28331	1212796	<5	<0.001	<0.005
28332	1212797	<5	<0.001	<0.005
28333	1212798	6	<0.001	0.006
28334	1212799	<5	<0.001	<0.005
28335 Dup	1212799	6	<0.001	0.006
28336	1212800	<5	<0.001	<0.005
28337	1212801	17	<0.001	0.017
28338	1212802	7	<0.001	0.007
28339	1212803	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Friday, February 24, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/10/2012
 Date Completed: 02/24/2012
 Job #: 201240294
 Reference: TL12231
 Sample #: 309

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
28340	1212804	<5	<0.001	<0.005
28341	1212805	5	<0.001	0.005
28342	1212806	6	<0.001	0.006
28343	1212807	<5	<0.001	<0.005
28344	1212808	5	<0.001	0.005
28345	1212809	9	<0.001	0.009
28346 Dup	1212809	8	<0.001	0.008
28347	1212810	258	0.008	0.258
28348	1212811	<5	<0.001	<0.005
28349	1212812	5	<0.001	0.005
28350	1212813	16	<0.001	0.016
28351	1212814	<5	<0.001	<0.005
28352	1212815	<5	<0.001	<0.005
28353	1212816	7	<0.001	0.007
28354	1212817	<5	<0.001	<0.005
28355	1212818	8	<0.001	0.008
28356	1212819	19	<0.001	0.019
28357 Rep	1212819	<5	<0.001	<0.005
28358	1212820	<5	<0.001	<0.005
28359	1212821	8	<0.001	0.008
28360	1212822	<5	<0.001	<0.005
28361	1212823	<5	<0.001	<0.005
28362	1212824	<5	<0.001	<0.005
28363	1212825	<5	<0.001	<0.005
28364	1212826	<5	<0.001	<0.005
28365	1212827	<5	<0.001	<0.005
28366	1212828	<5	<0.001	<0.005
28367	1212829	<5	<0.001	<0.005
28368 Dup	1212829	<5	<0.001	<0.005
28369	1212830	5104	0.149	5.104

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Friday, February 24, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/10/2012
 Date Completed: 02/24/2012
 Job #: 201240294
 Reference: TL12231
 Sample #: 309

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
28370	1212831	5	<0.001	0.005
28371	1212832	18	<0.001	0.018
28372	1212833	17	<0.001	0.017
28373	1212834	6	<0.001	0.006
28374	1212835	8	<0.001	0.008
28375	1212836	7	<0.001	0.007
28376	1212837	6	<0.001	0.006
28377	1212838	6	<0.001	0.006
28378	1212839	8	<0.001	0.008
28379 Dup	1212839	8	<0.001	0.008
28380	1212840	<5	<0.001	<0.005
28381	1212841	7	<0.001	0.007
28382	1212842	13	<0.001	0.013
28383	1212843	8	<0.001	0.008
28384	1212844	20	<0.001	0.020
28385	1212845	6	<0.001	0.006
28386	1212846	<5	<0.001	<0.005
28387	1212847	25	<0.001	0.025
28388	1212848	<5	<0.001	<0.005
28389	1212849	5	<0.001	0.005
28390 Dup	1212849	6	<0.001	0.006
28391	1212850	1089	0.032	1.089
28392	1212851	12	<0.001	0.012
28393	1212852	8	<0.001	0.008
28394	1212853	14	<0.001	0.014
28395	1212854	25	<0.001	0.025
28396	1212855	6	<0.001	0.006
28397	1212856	6	<0.001	0.006
28398	1212857	<5	<0.001	<0.005
28399	1212858	7	<0.001	0.007

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Friday, February 24, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/10/2012
 Date Completed: 02/24/2012
 Job #: 201240294
 Reference: TL12231
 Sample #: 309

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
28400	1212859	7	<0.001	0.007
28401 Dup	1212859	7	<0.001	0.007
28402	1212860	6	<0.001	0.006
28403	1212861	9	<0.001	0.009
28404	1212862	8	<0.001	0.008
28405	1212863	<5	<0.001	<0.005
28406	1212864	<5	<0.001	<0.005
28407	1212865	5	<0.001	0.005
28408	1212866	6	<0.001	0.006
28409	1212867	9	<0.001	0.009
28410	1212868	12	<0.001	0.012
28411	1212869	12	<0.001	0.012
28412 Dup	1212869	12	<0.001	0.012
28413	1212870	255	0.007	0.255
28414	1212871	6	<0.001	0.006
28415	1212872	6	<0.001	0.006
28416	1212873	9	<0.001	0.009
28417	1212874	<5	<0.001	<0.005
28418	1212875	<5	<0.001	<0.005
28419	1212876	<5	<0.001	<0.005
28420	1212877	<5	<0.001	<0.005
28421	1212878	<5	<0.001	<0.005
28422	1212879	<5	<0.001	<0.005
28423 Rep	1212879	<5	<0.001	<0.005
28424	1212880	<5	<0.001	<0.005
28425	1212881	<5	<0.001	<0.005
28426	1212882	<5	<0.001	<0.005
28427	1212883	<5	<0.001	<0.005
28428	1212884	<5	<0.001	<0.005
28429	1212885	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Friday, February 24, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/10/2012
 Date Completed: 02/24/2012
 Job #: 201240294
 Reference: TL12231
 Sample #: 309

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
28430	1212886	<5	<0.001	<0.005
28431	1212887	<5	<0.001	<0.005
28432	1212888	8	<0.001	0.008
28433	1212889	<5	<0.001	<0.005
28434 Dup	1212889	<5	<0.001	<0.005
28435	1212890	4808	0.140	4.808
28436	1212891	<5	<0.001	<0.005
28437	1212892	<5	<0.001	<0.005
28438	1212893	6	<0.001	0.006
28439	1212894	<5	<0.001	<0.005
28440	1212895	<5	<0.001	<0.005
28441	1212896	<5	<0.001	<0.005
28442	1212897	<5	<0.001	<0.005
28443	1212898	<5	<0.001	<0.005
28444	1212899	<5	<0.001	<0.005
28445 Dup	1212899	<5	<0.001	<0.005
28446	1212900	<5	<0.001	<0.005
28447	1212901	<5	<0.001	<0.005
28448	1212902	<5	<0.001	<0.005
28449	1212903	<5	<0.001	<0.005
28450	1212904	5	<0.001	0.005
28451	1212905	<5	<0.001	<0.005
28452	1212906	<5	<0.001	<0.005
28453	1212907	<5	<0.001	<0.005
28454	1212908	6	<0.001	0.006
28455	1212909	<5	<0.001	<0.005
28456 Dup	1212909	<5	<0.001	<0.005
28457	1212910	1285	0.037	1.285
28458	1212911	<5	<0.001	<0.005
28459	1212912	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Friday, February 24, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/10/2012
 Date Completed: 02/24/2012
 Job #: 201240294
 Reference: TL12231
 Sample #: 309

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
28460	1212913	5	<0.001	0.005
28461	1212914	<5	<0.001	<0.005
28462	1212915	<5	<0.001	<0.005
28463	1212916	8	<0.001	0.008
28464	1212917	8	<0.001	0.008
28465	1212918	7	<0.001	0.007
28466	1212919	9	<0.001	0.009
28467 Dup	1212919	83	0.002	0.083
28468	1212920	7	<0.001	0.007
28469	1212921	6	<0.001	0.006
28470	1212922	6	<0.001	0.006
28471	1212923	8	<0.001	0.008
28472	1212924	6	<0.001	0.006
28473	1212925	57	0.002	0.057
28474	1212926	89	0.003	0.089
28475	1212927	7	<0.001	0.007
28476	1212928	6	<0.001	0.006
28477	1212929	<5	<0.001	<0.005
28478 Dup	1212929	15	<0.001	0.015
28479	1212930	250	0.007	0.250
28480	1212931	14	<0.001	0.014
28481	1212932	7	<0.001	0.007
28482	1212933	7	<0.001	0.007
28483	1212934	195	0.006	0.195
28484	1212935	13	<0.001	0.013
28485	1212936	<5	<0.001	<0.005
28486	1212937	8	<0.001	0.008
28487	1212938	14	<0.001	0.014
28488	1212939	5	<0.001	0.005
28489 Rep	1212939	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Friday, February 24, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/10/2012
 Date Completed: 02/24/2012
 Job #: 201240294
 Reference: TL12231
 Sample #: 309

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
28490	1212940	<5	<0.001	<0.005
28491	1212941	<5	<0.001	<0.005
28492	1212942	<5	<0.001	<0.005
28493	1212943	<5	<0.001	<0.005
28494	1212944	<5	<0.001	<0.005
28495	1212945	<5	<0.001	<0.005
28496	1212946	<5	<0.001	<0.005
28497	1212947	7	<0.001	0.007
28498	1212948	13	<0.001	0.013

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianiuk H.Bac., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Wednesday, February 29, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/14/2012
 Date Completed: 02/29/2012
 Job #: 201240327
 Reference: TL11 232
 Sample #: 121

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
31100	1212949	9	<0.001	0.009
31101	1212950	4910	0.143	4.910
31102	1212951	12	<0.001	0.012
31103	1212952	7	<0.001	0.007
31104	1212953	44	0.001	0.044
31105	1212954	13	<0.001	0.013
31106	1212955	12	<0.001	0.012
31107	1212956	21	<0.001	0.021
31108	1212957	6	<0.001	0.006
31109	1212958	18	<0.001	0.018
31110 Dup	1212958	6	<0.001	0.006
31111	1212959	46	0.001	0.046
31112	1212960	9	<0.001	0.009
31113	1212961	17	<0.001	0.017
31114	1212962	8	<0.001	0.008
31115	1212963	12	<0.001	0.012
31116	1212964	9	<0.001	0.009
31117	1212965	9	<0.001	0.009
31118	1212966	10	<0.001	0.010
31119	1212967	8	<0.001	0.008
31120	1212968	9	<0.001	0.009
31121 Dup	1212968	11	<0.001	0.011
31122	1212969	8	<0.001	0.008
31123	1212970	1185	0.035	1.185
31124	1212971	14	<0.001	0.014
31125	1212972	11	<0.001	0.011
31126	1212973	11	<0.001	0.011
31127	1212974	12	<0.001	0.012
31128	1212975	16	<0.001	0.016
31129	1212976	35	0.001	0.035

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Wednesday, February 29, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/14/2012
 Date Completed: 02/29/2012
 Job #: 201240327
 Reference: TL11 232
 Sample #: 121

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
31130	1212977	22	<0.001	0.022
31131	1212978	30	<0.001	0.030
31132 Dup	1212978	33	<0.001	0.033
31133	1212979	38	0.001	0.038
31134	1212980	8	<0.001	0.008
31135	1212981	15	<0.001	0.015
31136	1212982	21	<0.001	0.021
31137	1212983	26	<0.001	0.026
31138	1212984	22	<0.001	0.022
31139	1212985	97	0.003	0.097
31140	1212986	33	<0.001	0.033
31141	1212987	23	<0.001	0.023
31142	1212988	18	<0.001	0.018
31143 Dup	1212988	16	<0.001	0.016
31144	1212989	12	<0.001	0.012
31145	1212990	282	0.008	0.282
31146	1212991	12	<0.001	0.012
31147	1212992	20	<0.001	0.020
31148	1212993	459	0.013	0.459
31149	1212994	27	<0.001	0.027
31150	1212995	30	<0.001	0.030
31151	1212996	18	<0.001	0.018
31152	1212997	11	<0.001	0.011
31153	1212998	246	0.007	0.246
31154 Dup	1212998	271	0.008	0.271
31155	1212999	12	<0.001	0.012
31156	1213000	8	<0.001	0.008
31157	1213001	11	<0.001	0.011
31158	1213002	23	<0.001	0.023
31159	1213003	85	0.002	0.085

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Wednesday, February 29, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/14/2012
 Date Completed: 02/29/2012
 Job #: 201240327
 Reference: TL11 232
 Sample #: 121

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
31160	1213004	11	<0.001	0.011
31161	1213005	13	<0.001	0.013
31162	1213006	10	<0.001	0.010
31163	1213007	15	<0.001	0.015
31164	1213008	32	<0.001	0.032
31165 Rep	1213008	10	<0.001	0.010
31166	1213009	43	0.001	0.043
31167	1213010	5000	0.146	5.000
31168	1213011	31	<0.001	0.031
31169	1213012	13	<0.001	0.013
31170	1213013	14	<0.001	0.014
31171	1213014	85	0.002	0.085
31172	1213015	36	0.001	0.036
31173	1213016	40	0.001	0.040
31174	1213017	1387	0.040	1.387
31175	1213018	219	0.006	0.219
31176 Dup	1213018	269	0.008	0.269
31177	1213019	210	0.006	0.210
31178	1213020	<5	<0.001	<0.005
31179	1213021	293	0.009	0.293
31180	1213022	189	0.006	0.189
31181	1213023	92	0.003	0.092
31182	1213024	1181	0.034	1.181
31183	1213025	281	0.008	0.281
31184	1213026	319	0.009	0.319
31185	1213027	212	0.006	0.212
31186	1213028	449	0.013	0.449
31187 Dup	1213028	568	0.017	0.568
31188	1213029	349	0.010	0.349
31189	1213030	1251	0.036	1.251

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Wednesday, February 29, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/14/2012
 Date Completed: 02/29/2012
 Job #: 201240327
 Reference: TL11 232
 Sample #: 121

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
31190	1213031	1754	0.051	1.754
31191	1213032	951	0.028	0.951
31192	1213033	390	0.011	0.390
31193	1213034	19	<0.001	0.019
31194	1213035	14	<0.001	0.014
31195	1213036	20	<0.001	0.020
31196	1213037	16	<0.001	0.016
31197	1213038	849	0.025	0.849
31198 Dup	1213038	771	0.023	0.771
31199	1213039	2617	0.076	2.617
31200	1213040	<5	<0.001	<0.005
31201	1213041	114	0.003	0.114
31202	1213042	13	<0.001	0.013
31203	1213043	58	0.002	0.058
31204	1213044	12	<0.001	0.012
31205	1213045	20	<0.001	0.020
31206	1213046	22	<0.001	0.022
31207	1213047	20	<0.001	0.020
31208	1213048	45	0.001	0.045
31209 Dup	1213048	47	0.001	0.047
31210	1213049	695	0.020	0.695
31211	1213050	274	0.008	0.274
31212	1213051	86	0.003	0.086
31213	1213052	377	0.011	0.377
31214	1213053	58	0.002	0.058
31215	1213054	150	0.004	0.150
31216	1213055	93	0.003	0.093
31217	1213056	51	0.001	0.051
31218	1213057	3828	0.112	3.828
31219	1213058	59	0.002	0.059

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Wednesday, February 29, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/14/2012
 Date Completed: 02/29/2012
 Job #: 201240327
 Reference: TL11 232
 Sample #: 121

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
31220 Dup	1213058	61	0.002	0.061
31221	1213059	102	0.003	0.102
31222	1213060	6	<0.001	0.006
31223	1213061	159	0.005	0.159
31224	1213062	73	0.002	0.073
31225	1213063	57	0.002	0.057
31226	1213064	139	0.004	0.139
31227	1213065	2914	0.085	2.914
31228	1213066	1192	0.035	1.192
31229	1213067	90	0.003	0.090
31230	1213068	43	0.001	0.043
31231 Rep	1213068	44	0.001	0.044
31232	1213069	801	0.023	0.801

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Thursday, March 8, 2012


Certificate of Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

Date Received: 02/16/2012
 Date Completed: 03/02/2012
 Job #: 201240365
 Reference: TL 12 233
 Sample #: 16

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
33817	1213070	5.042	<1	2.80	454	1334	2	11	2.33	<4	15	119	92	3.29	<0.01	14	1.10	458	8	53	887	26	1.36	37	<5	<10	224	1770	10	134	<10	15	215
33818	1213071	0.007	<1	4.54	25	583	3	10	2.16	<4	17	63	13	2.68	0.09	15	1.44	404	<1	63	738	22	0.87	<5	<5	<10	561	2514	3	67	98	9	175
33819	1213072	0.008	<1	3.95	14	475	2	14	1.63	<4	16	23	8	2.55	0.03	11	1.27	342	<1	37	671	17	0.98	<5	<5	<10	534	2571	2	62	<10	8	42
33820	1213073	0.008	<1	5.18	17	253	2	16	1.70	<4	15	22	15	2.67	<0.01	14	1.59	364	<1	37	757	19	0.94	<5	<5	<10	586	2736	4	68	<10	9	26
33821	1213074	0.013	<1	4.46	8	419	2	12	1.60	<4	13	21	12	2.32	<0.01	19	1.18	347	<1	37	668	14	0.71	<5	<5	<10	576	2517	8	61	<10	8	17
33822	1213075	0.012	<1	5.51	10	312	2	7	1.93	<4	13	22	10	2.28	0.14	19	1.12	356	<1	36	673	18	0.66	6	<5	<10	636	2526	2	62	<10	8	147
33823	1213076	0.008	<1	5.37	15	292	2	10	1.91	<4	14	21	8	2.31	0.10	19	1.23	337	<1	32	688	20	0.62	<5	<5	<10	644	2596	3	62	<10	8	46
33824	1213077	0.008	<1	4.40	12	449	2	4	2.01	<4	14	22	6	2.39	0.03	15	1.15	323	<1	38	673	18	0.65	<5	<5	<10	686	2541	2	61	<10	8	14
33825	1213078	0.011	<1	5.09	9	704	2	9	1.81	<4	17	20	<1	2.57	<0.01	19	1.21	314	<1	35	714	9	0.89	<5	<5	<10	588	2696	3	63	<10	8	22
33826	1213079	0.013	<1	0.99	12	586	<2	23	1.52	4	14	16	99	2.27	<0.01	6	0.78	287	12	107	559	15	1.02	<5	9	<10	564	2526	<2	56	<10	5	376
33827D	1213079	0.008	<1	0.61	12	632	<2	3	1.57	<4	15	17	95	2.36	<0.01	6	0.79	297	6	113	574	15	1.02	<5	6	<10	587	2602	<2	58	<10	5	178
33828	1213080	<0.005	<1	3.81	9	433	2	7	1.61	<4	14	31	21	2.36	<0.01	8	0.88	436	<1	24	577	8	0.43	<5	<5	<10	290	2075	4	85	25	14	24
33829	1213081	<0.005	<1	4.84	9	506	2	<1	2.01	<4	16	21	<1	2.61	0.06	17	1.13	302	<1	36	660	9	0.69	<5	<5	<10	617	2532	<2	63	<10	8	16
33830	1213082	0.010	<1	4.46	9	525	2	11	2.20	<4	12	18	<1	2.17	0.05	15	0.95	276	<1	28	621	6	0.54	<5	<5	<10	565	2375	<2	56	<10	7	11
33831	1213083	<0.005	<1	4.66	4	521	2	10	2.02	<4	12	20	3	2.31	<0.01	14	1.10	315	<1	34	649	8	0.42	<5	<5	<10	663	2541	2	62	<10	8	15
33832	1213084	<0.005	<1	4.94	4	560	2	13	2.21	<4	13	20	26	2.53	0.03	11	1.23	376	<1	34	710	9	0.41	<5	<5	<10	723	2565	2	66	<10	9	19
33833	1213085	<0.005	<1	4.66	15	937	3	16	0.91	<4	12	87	25	2.07	0.16	24	1.39	317	<1	50	742	12	0.41	<5	<5	<10	356	1773	4	54	<10	9	17

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, March 6, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/16/2012
 Date Completed: 03/02/2012
 Job #: 201240365
 Reference: TL 12 233
 Sample #: 16

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
33817	1213070	5042	0.147	5.042
33818	1213071	7	<0.001	0.007
33819	1213072	8	<0.001	0.008
33820	1213073	8	<0.001	0.008
33821	1213074	13	<0.001	0.013
33822	1213075	12	<0.001	0.012
33823	1213076	8	<0.001	0.008
33824	1213077	8	<0.001	0.008
33825	1213078	11	<0.001	0.011
33826	1213079	13	<0.001	0.013
33827 Dup	1213079	8	<0.001	0.008
33828	1213080	<5	<0.001	<0.005
33829	1213081	<5	<0.001	<0.005
33830	1213082	10	<0.001	0.010
33831	1213083	<5	<0.001	<0.005
33832	1213084	<5	<0.001	<0.005
33833	1213085	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AlSu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Wednesday, February 29, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/16/2012
 Date Completed: 02/29/2012
 Job #: 201240366
 Reference: TL 12 234
 Sample #: 107

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
33834	1213086	60	0.002	0.060
33835	1213087	14	<0.001	0.014
33836	1213088	480	0.014	0.480
33837	1213089	18	<0.001	0.018
33838	1213090	1002	0.029	1.002
33839	1213091	14	<0.001	0.014
33840	1213092	14	<0.001	0.014
33841	1213093	50	0.001	0.050
33842	1213094	11	<0.001	0.011
33843	1213095	15	<0.001	0.015
33844 Dup	1213095	10	<0.001	0.010
33845	1213096	7	<0.001	0.007
33846	1213097	9	<0.001	0.009
33847	1213098	14	<0.001	0.014
33848	1213099	518	0.015	0.518
33849	1213100	7	<0.001	0.007
33850	1213101	64	0.002	0.064
33851	1213102	1602	0.047	1.602
33852	1213103	233	0.007	0.233
33853	1213104	8	<0.001	0.008
33854	1213105	12	<0.001	0.012
33855 Dup	1213105	14	<0.001	0.014
33856	1213106	7	<0.001	0.007
33857	1213107	7	<0.001	0.007
33858	1213108	<5	<0.001	<0.005
33859	1213109	9	<0.001	0.009
33860	1213110	245	0.007	0.245
33861	1213111	7	<0.001	0.007
33862	1213112	53	0.002	0.053
33863	1213113	113	0.003	0.113

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Wednesday, February 29, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/16/2012
 Date Completed: 02/29/2012
 Job #: 201240366
 Reference: TL 12 234
 Sample #: 107

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
33864	1213114	7638	0.223	7.638
33865	1213115	300	0.009	0.300
33866 Dup	1213115	302	0.009	0.302
33867	1213116	337	0.010	0.337
33868	1213117	445	0.013	0.445
33869	1213118	155	0.005	0.155
33870	1213119	52	0.002	0.052
33871	1213120	<5	<0.001	<0.005
33872	1213121	274	0.008	0.274
33873	1213122	11	<0.001	0.011
33874	1213123	10	<0.001	0.010
33875	1213124	32	<0.001	0.032
33876	1213125	16	<0.001	0.016
33877 Dup	1213125	17	<0.001	0.017
33878	1213126	58	0.002	0.058
33879	1213127	22	<0.001	0.022
33880	1213128	17	<0.001	0.017
33881	1213129	35	0.001	0.035
33882	1213130	5016	0.146	5.016
33883	1213131	24	<0.001	0.024
33884	1213132	243	0.007	0.243
33885	1213133	41	0.001	0.041
33886	1213134	32	<0.001	0.032
33887	1213135	113	0.003	0.113
33888 Dup	1213135	73	0.002	0.073
33889	1213136	119	0.003	0.119
33890	1213137	3139	0.092	3.139
33891	1213138	324	0.009	0.324
33892	1213139	452	0.013	0.452
33893	1213140	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Wednesday, February 29, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/16/2012
 Date Completed: 02/29/2012
 Job #: 201240366
 Reference: TL 12 234
 Sample #: 107

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
33894	1213141	333	0.010	0.333
33895	1213142	338	0.010	0.338
33896	1213143	53	0.002	0.053
33897	1213144	39	0.001	0.039
33898	1213145	165	0.005	0.165
33899 Rep	1213145	178	0.005	0.178
33900	1213146	41	0.001	0.041
33901	1213147	108	0.003	0.108
33902	1213148	65	0.002	0.065
33903	1213149	90	0.003	0.090
33904	1213150	1204	0.035	1.204
33905	1213151	414	0.012	0.414
33906	1213152	54	0.002	0.054
33907	1213153	44	0.001	0.044
33908	1213154	53	0.002	0.053
33909	1213155	69	0.002	0.069
33910 Dup	1213155	64	0.002	0.064
33911	1213156	60	0.002	0.060
33912	1213157	381	0.011	0.381
33913	1213158	307	0.009	0.307
33914	1213159	377	0.011	0.377
33915	1213160	<5	<0.001	<0.005
33916	1213161	71	0.002	0.071
33917	1213162	94	0.003	0.094
33918	1213163	23	<0.001	0.023
33919	1213164	29	<0.001	0.029
33920	1213165	44	0.001	0.044
33921 Dup	1213165	36	0.001	0.036
33922	1213166	18	<0.001	0.018
33923	1213167	25	<0.001	0.025

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Wednesday, February 29, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/16/2012
 Date Completed: 02/29/2012
 Job #: 201240366
 Reference: TL 12 234
 Sample #: 107

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
33924	1213168	14	<0.001	0.014
33925	1213169	12	<0.001	0.012
33926	1213170	311	0.009	0.311
33927	1213171	66	0.002	0.066
33928	1213172	36	0.001	0.036
33929	1213173	94	0.003	0.094
33930	1213174	692	0.020	0.692
33931	1213175	72	0.002	0.072
33932 Dup	1213175	76	0.002	0.076
33933	1213176	54	0.002	0.054
33934	1213177	153	0.004	0.153
33935	1213178	59	0.002	0.059
33936	1213179	113	0.003	0.113
33937	1213180	5	<0.001	0.005
33938	1213181	39	0.001	0.039
33939	1213182	36	0.001	0.036
33940	1213183	149	0.004	0.149
33941	1213184	49	0.001	0.049
33942	1213185	12	<0.001	0.012
33943 Dup	1213185	11	<0.001	0.011
33944	1213186	469	0.014	0.469
33945	1213187	1008	0.029	1.008
33946	1213188	22	<0.001	0.022
33947	1213189	58	0.002	0.058
33948	1213190	4772	0.139	4.772
33949	1213191	66	0.002	0.066
33950	1213192	46	0.001	0.046

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianiuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, March 6, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/21/2012
 Date Completed: 03/06/2012
 Job #: 201240407
 Reference: TL 12 235
 Sample #: 86

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
36360	1213193	12	<0.001	0.012
36361	1213194	20	<0.001	0.020
36362	1213195	19	<0.001	0.019
36363	1213196	20	<0.001	0.020
36364	1213197	171	0.005	0.171
36365	1213198	16	<0.001	0.016
36366	1213199	22	<0.001	0.022
36367	1213200	9	<0.001	0.009
36368	1213201	21	<0.001	0.021
36369	1213202	103	0.003	0.103
36370 Dup	1213202	128	0.004	0.128
36371	1213203	37	0.001	0.037
36372	1213204	20	<0.001	0.020
36373	1213205	41	0.001	0.041
36374	1213206	78	0.002	0.078
36375	1213207	145	0.004	0.145
36376	1213208	68	0.002	0.068
36377	1213209	555	0.016	0.555
36378	1213210	1179	0.034	1.179
36379	1213211	665	0.019	0.665
36380	1213212	37	0.001	0.037
36381 Dup	1213212	62	0.002	0.062
36382	1213213	17	<0.001	0.017
36383	1213214	54	0.002	0.054
36384	1213215	35	0.001	0.035
36385	1213216	26	<0.001	0.026
36386	1213217	377	0.011	0.377
36387	1213218	2924	0.085	2.924
36388	1213219	465	0.014	0.465
36389	1213220	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, March 6, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/21/2012
 Date Completed: 03/06/2012
 Job #: 201240407
 Reference: TL 12 235
 Sample #: 86

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
36390	1213221	280	0.008	0.280
36391	1213222	90	0.003	0.090
36392 Dup	1213222	159	0.005	0.159
36393	1213223	33	<0.001	0.033
36394	1213224	11	<0.001	0.011
36395	1213225	14	<0.001	0.014
36396	1213226	95	0.003	0.095
36397	1213227	<5	<0.001	<0.005
36398	1213228	<5	<0.001	<0.005
36399	1213251	22	<0.001	0.022
36400	1213252	114	0.003	0.114
36401	1213253	94	0.003	0.094
36402	1213254	20	<0.001	0.020
36403 Dup	1213254	23	<0.001	0.023
36404	1213255	9	<0.001	0.009
36405	1213256	27	<0.001	0.027
36406	1213257	25	<0.001	0.025
36407	1213258	16	<0.001	0.016
36408	1213259	25	<0.001	0.025
36409	1213260	1224	0.036	1.224
36410	1213261	49	0.001	0.049
36411	1213262	20	<0.001	0.020
36412	1213263	84	0.002	0.084
36413	1213264	42	0.001	0.042
36414 Dup	1213264	76	0.002	0.076
36415	1213265	36	0.001	0.036
36416	1213266	24	<0.001	0.024
36417	1213267	13	<0.001	0.013
36418	1213268	26	<0.001	0.026
36419	1213269	40	0.001	0.040

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, March 6, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/21/2012
 Date Completed: 03/06/2012
 Job #: 201240407
 Reference: TL 12 235
 Sample #: 86

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
36420	1213270	10	<0.001	0.010
36421	1213271	19	<0.001	0.019
36422	1213272	14	<0.001	0.014
36423	1213273	13	<0.001	0.013
36424	1213274	74	0.002	0.074
36425 Rep	1213274	67	0.002	0.067
36426	1213275	23	<0.001	0.023
36427	1213276	161	0.005	0.161
36428	1213277	14	<0.001	0.014
36429	1213278	18	<0.001	0.018
36430	1213279	12	<0.001	0.012
36431	1213280	308	0.009	0.308
36432	1213281	20	<0.001	0.020
36433	1213282	291	0.008	0.291
36434	1213283	42	0.001	0.042
36435	1213284	25	<0.001	0.025
36436 Dup	1213284	14	<0.001	0.014
36437	1213285	46	0.001	0.046
36438	1213286	70	0.002	0.070
36439	1213287	83	0.002	0.083
36440	1213288	187	0.005	0.187
36441	1213289	48	0.001	0.048
36442	1213290	<5	<0.001	<0.005
36443	1213291	61	0.002	0.061
36444	1213292	14	<0.001	0.014
36445	1213293	54	0.002	0.054
36446	1213294	51	0.002	0.051
36447 Dup	1213294	53	0.002	0.053
36448	1213295	69	0.002	0.069
36449	1213296	47	0.001	0.047

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, March 6, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/21/2012
 Date Completed: 03/06/2012
 Job #: 201240407
 Reference: TL 12 235
 Sample #: 86

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
36450	1213297	8	<0.001	0.008
36451	1213298	30	<0.001	0.030
36452	1213299	68	0.002	0.068
36453	1213300	4832	0.141	4.832

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianiuk H.Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Thursday, March 8, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/23/2012
 Date Completed: 03/08/2012
 Job #: 201240450
 Reference: TL12 236
 Sample #: 66

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
40379	1213229	17	<0.001	0.017
40380	1213230	250	0.007	0.250
40381	1213231	455	0.013	0.455
40382	1213232	934	0.027	0.934
40383	1213233	94	0.003	0.094
40384	1213234	299	0.009	0.299
40385	1213235	1464	0.043	1.464
40386	1213236	1027	0.030	1.027
40387	1213237	51	0.001	0.051
40388	1213238	256	0.007	0.256
40389 Dup	1213238	338	0.010	0.338
40390	1213239	17	<0.001	0.017
40391	1213240	6	<0.001	0.006
40392	1213241	66	0.002	0.066
40393	1213242	6	<0.001	0.006
40394	1213243	6	<0.001	0.006
40395	1213244	7	<0.001	0.007
40396	1213245	10	<0.001	0.010
40397	1213246	21	<0.001	0.021
40398	1213247	52	0.002	0.052
40399	1213248	22	<0.001	0.022
40400 Dup	1213248	16	<0.001	0.016
40401	1213249	19	<0.001	0.019
40402	1213250	5008	0.146	5.008
40403	1213301	7	<0.001	0.007
40404	1213302	26	<0.001	0.026
40405	1213303	146	0.004	0.146
40406	1213304	12	<0.001	0.012
40407	1213305	44	0.001	0.044
40408	1213306	36	0.001	0.036

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Thursday, March 8, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/23/2012
 Date Completed: 03/08/2012
 Job #: 201240450
 Reference: TL12 236
 Sample #: 66

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
40409	1213307	73	0.002	0.073
40410	1213308	8	<0.001	0.008
40411 Dup	1213308	9	<0.001	0.009
40412	1213309	30	<0.001	0.030
40413	1213310	<5	<0.001	<0.005
40414	1213311	220	0.006	0.220
40415	1213312	7	<0.001	0.007
40416	1213313	12	<0.001	0.012
40417	1213314	8	<0.001	0.008
40418	1213315	91	0.003	0.091
40419	1213316	112	0.003	0.112
40420	1213317	30	<0.001	0.030
40421	1213318	20	<0.001	0.020
40422 Dup	1213318	24	<0.001	0.024
40423	1213319	28	<0.001	0.028
40424	1213320	1127	0.033	1.127
40425	1213321	57	0.002	0.057
40426	1213322	118	0.003	0.118
40427	1213323	168	0.005	0.168
40428	1213324	44	0.001	0.044
40429	1213325	12	<0.001	0.012
40430	1213326	10	<0.001	0.010
40431	1213327	<5	<0.001	<0.005
40432	1213328	<5	<0.001	<0.005
40433 Dup	1213328	<5	<0.001	<0.005
40434	1213329	11	<0.001	0.011
40435	1213330	<5	<0.001	<0.005
40436	1213331	56	0.002	0.056
40437	1213332	805	0.023	0.805
40438	1213333	10	<0.001	0.010

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Thursday, March 8, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/23/2012
 Date Completed: 03/08/2012
 Job #: 201240450
 Reference: TL12 236
 Sample #: 66

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
40439	1213334	13	<0.001	0.013
40440	1213335	1060	0.031	1.060
40441	1213336	558	0.016	0.558
40442	1213337	85	0.002	0.085
40443	1213338	179	0.005	0.179
40444 Rep	1213338	178	0.005	0.178
40445	1213339	65	0.002	0.065
40446	1213340	247	0.007	0.247
40447	1213341	21	<0.001	0.021
40448	1213342	18	<0.001	0.018
40449	1213343	13	<0.001	0.013
40450	1213344	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianliuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, March 6, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/23/2012
 Date Completed: 03/06/2012
 Job #: 201240449
 Reference: TL12 237
 Sample #: 115

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
40253	1213345	6	<0.001	0.006
40254	1213346	40	0.001	0.040
40255	1213347	23	<0.001	0.023
40256	1213348	6	<0.001	0.006
40257	1213349	8	<0.001	0.008
40258	1213350	<5	<0.001	<0.005
40259	1213351	9	<0.001	0.009
40260	1213352	41	0.001	0.041
40261	1213353	13	<0.001	0.013
40262	1213354	78	0.002	0.078
40263 Dup	1213354	92	0.003	0.092
40264	1213355	21	<0.001	0.021
40265	1213356	17	<0.001	0.017
40266	1213357	14	<0.001	0.014
40267	1213358	7	<0.001	0.007
40268	1213359	9	<0.001	0.009
40269	1213360	5066	0.148	5.066
40270	1213361	22	<0.001	0.022
40271	1213362	90	0.003	0.090
40272	1213363	18	<0.001	0.018
40273	1213364	9	<0.001	0.009
40274 Dup	1213364	7	<0.001	0.007
40275	1213365	<5	<0.001	<0.005
40276	1213366	<5	<0.001	<0.005
40277	1213367	10	<0.001	0.010
40278	1213368	11	<0.001	0.011
40279	1213369	382	0.011	0.382
40280	1213370	7	<0.001	0.007
40281	1213371	536	0.016	0.536
40282	1213372	432	0.013	0.432

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, March 6, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/23/2012
 Date Completed: 03/06/2012
 Job #: 201240449
 Reference: TL12 237
 Sample #: 115

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
40283	1213373	103	0.003	0.103
40284	1213374	26	<0.001	0.026
40285 Dup	1213374	25	<0.001	0.025
40286	1213375	102	0.003	0.102
40287	1213376	118	0.003	0.118
40288	1213377	36	0.001	0.036
40289	1213378	<5	<0.001	<0.005
40290	1213379	66	0.002	0.066
40291	1213380	1178	0.034	1.178
40292	1213381	10	<0.001	0.010
40293	1213382	5	<0.001	0.005
40294	1213383	<5	<0.001	<0.005
40295	1213384	<5	<0.001	<0.005
40296 Dup	1213384	<5	<0.001	<0.005
40297	1213385	<5	<0.001	<0.005
40298	1213386	45	0.001	0.045
40299	1213387	19	<0.001	0.019
40300	1213388	24	<0.001	0.024
40301	1213389	165	0.005	0.165
40302	1213390	7	<0.001	0.007
40303	1213391	76	0.002	0.076
40304	1213392	79	0.002	0.079
40305	1213393	87	0.003	0.087
40306	1213394	21	<0.001	0.021
40307 Dup	1213394	21	<0.001	0.021
40308	1213395	87	0.003	0.087
40309	1213396	99	0.003	0.099
40310	1213397	25	<0.001	0.025
40311	1213398	29	<0.001	0.029
40312	1213399	15	<0.001	0.015

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, March 6, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/23/2012
 Date Completed: 03/06/2012
 Job #: 201240449
 Reference: TL12 237
 Sample #: 115

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
40313	1213400	236	0.007	0.236
40314	1213401	70	0.002	0.070
40315	1213402	18	<0.001	0.018
40316	1213403	145	0.004	0.145
40317	1213404	42	0.001	0.042
40318 Rep	1213404	12	<0.001	0.012
40319	1213405	15	<0.001	0.015
40320	1213406	<5	<0.001	<0.005
40321	1213407	32	<0.001	0.032
40322	1213408	<5	<0.001	<0.005
40323	1213409	9	<0.001	0.009
40324	1213410	<5	<0.001	<0.005
40325	1213411	30	<0.001	0.030
40326	1213412	8	<0.001	0.008
40327	1213413	17	<0.001	0.017
40328	1213414	39	0.001	0.039
40329 Dup	1213414	21	<0.001	0.021
40330	1213415	270	0.008	0.270
40331	1213416	173	0.005	0.173
40332	1213417	156	0.005	0.156
40333	1213418	453	0.013	0.453
40334	1213419	382	0.011	0.382
40335	1213420	5011	0.146	5.011
40336	1213421	338	0.010	0.338
40337	1213422	56	0.002	0.056
40338	1213423	123	0.004	0.123
40339	1213424	71	0.002	0.071
40340 Dup	1213424	79	0.002	0.079
40341	1213425	525	0.015	0.525
40342	1213426	62	0.002	0.062

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, March 6, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

 Date Received: 02/23/2012
 Date Completed: 03/06/2012
 Job #: 201240449
 Reference: TL12 237
 Sample #: 115

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
40343	1213427	20	<0.001	0.020
40344	1213428	35	0.001	0.035
40345	1213429	15	<0.001	0.015
40346	1213430	7	<0.001	0.007
40347	1213431	47	0.001	0.047
40348	1213432	689	0.020	0.689
40349	1213433	1475	0.043	1.475
40350	1213434	32	<0.001	0.032
40351 Dup	1213434	43	0.001	0.043
40352	1213435	50	0.001	0.050
40353	1213436	40	0.001	0.040
40354	1213437	165	0.005	0.165
40355	1213438	176	0.005	0.176
40356	1213439	145	0.004	0.145
40357	1213440	1276	0.037	1.276
40358	1213441	427	0.012	0.427
40359	1213442	115	0.003	0.115
40360	1213443	228	0.007	0.228
40361	1213444	230	0.007	0.230
40362 Dup	1213444	218	0.006	0.218
40363	1213445	191	0.006	0.191
40364	1213446	223	0.006	0.223
40365	1213447	177	0.005	0.177
40366	1213448	324	0.009	0.324
40367	1213449	71	0.002	0.071
40368	1213450	<5	<0.001	<0.005
40369	1213451	291	0.008	0.291
40370	1213452	16	<0.001	0.016
40371	1213453	49	0.001	0.049
40372	1213454	277	0.008	0.277

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, March 6, 2012

Certificate of Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, jselway@cciconline.ca

Date Received: 02/23/2012
 Date Completed: 03/06/2012
 Job #: 201240449
 Reference: TL12 237
 Sample #: 115

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
40373 Dup	1213454	315	0.009	0.315
40374	1213455	530	0.015	0.530
40375	1213456	191	0.006	0.191
40376	1213457	52	0.002	0.052
40377	1213458	61	0.002	0.061
40378	1213459	41	0.001	0.041

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Friday, March 16, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 03/05/2012
 Date Completed: 03/16/2012
 Job #: 201240667
 Reference: TL 12 238
 Sample #: 155

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
60199	1213460	267	0.008	0.267
60200	1213461	10	<0.001	0.010
60201	1213462	<5	<0.001	<0.005
60202	1213463	209	0.006	0.209
60203	1213464	18	<0.001	0.018
60204	1213465	24	<0.001	0.024
60205	1213466	12	<0.001	0.012
60206	1213467	113	0.003	0.113
60207	1213468	13	<0.001	0.013
60208	1213469	7	<0.001	0.007
60209 Dup	1213469	10	<0.001	0.010
60210	1213470	<5	<0.001	<0.005
60211	1213471	10	<0.001	0.010
60212	1213472	8	<0.001	0.008
60213	1213473	19	<0.001	0.019
60214	1213474	15	<0.001	0.015
60215	1213475	107	0.003	0.107
60216	1213476	108	0.003	0.108
60217	1213477	50	0.001	0.050
60218	1213478	66	0.002	0.066
60219	1213479	1118	0.033	1.118
60220 Dup	1213479	1225	0.036	1.225
60221	1213480	5574	0.163	5.574
60222	1213481	67	0.002	0.067
60223	1213482	302	0.009	0.302
60224	1213483	55	0.002	0.055
60225	1213484	457	0.013	0.457
60226	1213485	40	0.001	0.040
60227	1213486	57	0.002	0.057
60228	1213487	42	0.001	0.042

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Friday, March 16, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 03/05/2012
 Date Completed: 03/16/2012
 Job #: 201240667
 Reference: TL 12 238
 Sample #: 155

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
60229	1213488	67	0.002	0.067
60230	1213489	167	0.005	0.167
60231 Dup	1213489	212	0.006	0.212
60232	1213490	<5	<0.001	<0.005
60233	1213491	2574	0.075	2.574
60234	1213492	11	<0.001	0.011
60235	1213493	5	<0.001	0.005
60236	1213494	17	<0.001	0.017
60237	1213495	11	<0.001	0.011
60238	1213496	9	<0.001	0.009
60239	1213497	7	<0.001	0.007
60240	1213498	5	<0.001	0.005
60241	1213499	<5	<0.001	<0.005
60242 Dup	1213499	<5	<0.001	<0.005
60243	1213500	1097	0.032	1.097
60244	1213501	<5	<0.001	<0.005
60245	1213502	<5	<0.001	<0.005
60246	1213503	<5	<0.001	<0.005
60247	1213504	<5	<0.001	<0.005
60248	1213505	7	<0.001	0.007
60249	1213506	<5	<0.001	<0.005
60250	1213507	7	<0.001	0.007
60251	1213508	5	<0.001	0.005
60252	1213509	<5	<0.001	<0.005
60253 Dup	1213509	<5	<0.001	<0.005
60254	1213510	<5	<0.001	<0.005
60255	1213511	9	<0.001	0.009
60256	1213512	10	<0.001	0.010
60257	1213513	8	<0.001	0.008
60258	1213514	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Friday, March 16, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 03/05/2012
 Date Completed: 03/16/2012
 Job #: 201240667
 Reference: TL 12 238
 Sample #: 155

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
60259	1213515	7	<0.001	0.007
60260	1213516	<5	<0.001	<0.005
60261	1213517	26	<0.001	0.026
60262	1213518	25	<0.001	0.025
60263	1213519	235	0.007	0.235
60264 Rep	1213519	164	0.005	0.164
60265	1213520	241	0.007	0.241
60266	1213521	51	0.001	0.051
60267	1213522	64	0.002	0.064
60268	1213523	79	0.002	0.079
60269	1213524	37	0.001	0.037
60270	1213525	51	0.001	0.051
60271	1213526	116	0.003	0.116
60272	1213527	61	0.002	0.061
60273	1213528	81	0.002	0.081
60274	1213529	990	0.029	0.990
60275 Dup	1213529	1052	0.031	1.052
60276	1213530	6	<0.001	0.006
60277	1213531	433	0.013	0.433
60278	1213532	107	0.003	0.107
60279	1213533	478	0.014	0.478
60280	1213534	1646	0.048	1.646
60281	1213535	228	0.007	0.228
60282	1213536	58	0.002	0.058
60283	1213537	34	<0.001	0.034
60284	1213538	47	0.001	0.047
60285	1213539	49	0.001	0.049
60286 Dup	1213539	59	0.002	0.059
60287	1213540	5141	0.150	5.141
60288	1213541	41	0.001	0.041

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Friday, March 16, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 03/05/2012
 Date Completed: 03/16/2012
 Job #: 201240667
 Reference: TL 12 238
 Sample #: 155

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
60289	1213542	26	<0.001	0.026
60290	1213543	50	0.001	0.050
60291	1213544	51	0.001	0.051
60292	1213545	3194	0.093	3.194
60293	1213546	652	0.019	0.652
60294	1213547	232	0.007	0.232
60295	1213548	197	0.006	0.197
60296	1213549	151	0.004	0.151
60297 Dup	1213549	162	0.005	0.162
60298	1213550	7	<0.001	0.007
60299	1213551	82	0.002	0.082
60300	1213552	92	0.003	0.092
60301	1213553	328	0.010	0.328
60302	1213554	385	0.011	0.385
60303	1213555	252	0.007	0.252
60304	1213556	615	0.018	0.615
60305	1213557	65	0.002	0.065
60306	1213558	61	0.002	0.061
60307	1213559	77	0.002	0.077
60308 Dup	1213559	49	0.001	0.049
60309	1213560	1150	0.034	1.150
60310	1213561	25	<0.001	0.025
60311	1213562	70	0.002	0.070
60312	1213563	62	0.002	0.062
60313	1213564	361	0.011	0.361
60314	1213565	70	0.002	0.070
60315	1213566	58	0.002	0.058
60316	1213567	95	0.003	0.095
60317	1213568	156	0.005	0.156
60318	1213569	33	<0.001	0.033

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Friday, March 16, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 03/05/2012
 Date Completed: 03/16/2012
 Job #: 201240667
 Reference: TL 12 238
 Sample #: 155

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
60319 Dup	1213569	38	0.001	0.038
60320	1213570	<5	<0.001	<0.005
60321	1213571	347	0.010	0.347
60322	1213572	55	0.002	0.055
60323	1213573	46	0.001	0.046
60324	1213574	64	0.002	0.064
60325	1213575	79	0.002	0.079
60326	1213576	189	0.006	0.189
60327	1213577	42	0.001	0.042
60328	1213578	94	0.003	0.094
60329	1213579	335	0.010	0.335
60330 Rep	1213579	346	0.010	0.346
60331	1213580	252	0.007	0.252
60332	1213581	28	<0.001	0.028
60333	1213582	38	0.001	0.038
60334	1213583	130	0.004	0.130
60335	1213584	46	0.001	0.046
60336	1213585	129	0.004	0.129
60337	1213586	30	<0.001	0.030
60338	1213587	18	<0.001	0.018
60339	1213588	15	<0.001	0.015
60340	1213589	25	<0.001	0.025
60341 Dup	1213589	41	0.001	0.041
60342	1213590	5	<0.001	0.005
60343	1213591	24	<0.001	0.024
60344	1213592	23	<0.001	0.023
60345	1213593	40	0.001	0.040
60346	1213594	60	0.002	0.060
60347	1213595	112	0.003	0.112
60348	1213596	59	0.002	0.059

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Friday, March 16, 2012

Certificate of Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 03/05/2012
 Date Completed: 03/16/2012
 Job #: 201240667
 Reference: TL 12 238
 Sample #: 155

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
60349	1213597	638	0.019	0.638
60350	1213598	189	0.006	0.189
60351	1213599	30	<0.001	0.030
60352 Dup	1213599	35	0.001	0.035
60353	1213600	5065	0.148	5.065
60354	1213601	5	<0.001	0.005
60355	1213602	<5	<0.001	<0.005
60356	1213603	<5	<0.001	<0.005
60357	1213604	<5	<0.001	<0.005
60358	1213605	<5	<0.001	<0.005
60359	1213606	12	<0.001	0.012
60360	1213607	12	<0.001	0.012
60361	1213608	24	<0.001	0.024
60362	1213609	15	<0.001	0.015
60363 Dup	1213609	14	<0.001	0.014
60364	1213610	8	<0.001	0.008
60365	1213611	22	<0.001	0.022
60366	1213612	8	<0.001	0.008
60367	1213613	11	<0.001	0.011
60368	1213614	12	<0.001	0.012

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianiuk H. B.Sc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, March 20, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 03/06/2012
 Date Completed: 03/20/2012
 Job #: 201240685
 Reference: TL 12 239
 Sample #: 151

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
62346	1213615	107	0.003	0.107
62347	1213616	106	0.003	0.106
62348	1213617	18	<0.001	0.018
62349	1213618	16	<0.001	0.016
62350	1213619	887	0.026	0.887
62351	1213620	1198	0.035	1.198
62352	1213621	172	0.005	0.172
62353	1213622	59	0.002	0.059
62354	1213623	87	0.003	0.087
62355	1213624	591	0.017	0.591
62356 Dup	1213624	594	0.017	0.594
62357	1213625	806	0.024	0.806
62358	1213626	48	0.001	0.048
62359	1213627	13	<0.001	0.013
62360	1213628	<5	<0.001	<0.005
62361	1213629	63	0.002	0.063
62362	1213630	<5	<0.001	<0.005
62363	1213631	<5	<0.001	<0.005
62364	1213632	<5	<0.001	<0.005
62365	1213633	<5	<0.001	<0.005
62366	1213634	8	<0.001	0.008
62367 Dup	1213634	9	<0.001	0.009
62368	1213635	73	0.002	0.073
62369	1213636	121	0.004	0.121
62370	1213637	9	<0.001	0.009
62371	1213638	7	<0.001	0.007
62372	1213639	<5	<0.001	<0.005
62373	1213640	253	0.007	0.253
62374	1213641	<5	<0.001	<0.005
62375	1213642	7	<0.001	0.007

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, March 20, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 03/06/2012
 Date Completed: 03/20/2012
 Job #: 201240685
 Reference: TL 12 239
 Sample #: 151

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
62376	1213643	10	<0.001	0.010
62377	1213644	<5	<0.001	<0.005
62378 Dup	1213644	6	<0.001	0.006
62379	1213645	<5	<0.001	<0.005
62380	1213646	8	<0.001	0.008
62381	1213647	39	0.001	0.039
62382	1213648	37	0.001	0.037
62383	1213649	19	<0.001	0.019
62384	1213650	<5	<0.001	<0.005
62385	1213651	149	0.004	0.149
62386	1213652	69	0.002	0.069
62387	1213653	33	<0.001	0.033
62388	1213654	170	0.005	0.170
62389 Dup	1213654	156	0.005	0.156
62390	1213655	131	0.004	0.131
62391	1213656	179	0.005	0.179
62392	1213657	193	0.006	0.193
62393	1213658	681	0.020	0.681
62394	1213659	74	0.002	0.074
62395	1213660	4833	0.141	4.833
62396	1213661	220	0.006	0.220
62397	1213662	47	0.001	0.047
62398	1213663	81	0.002	0.081
62399	1213664	206	0.006	0.206
62400 Dup	1213664	251	0.007	0.251
62401	1213665	703	0.021	0.703
62402	1213666	81	0.002	0.081
62403	1213667	49	0.001	0.049
62404	1213668	141	0.004	0.141
62405	1213669	137	0.004	0.137

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, March 20, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 03/06/2012
 Date Completed: 03/20/2012
 Job #: 201240685
 Reference: TL 12 239
 Sample #: 151

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
62406	1213670	8	<0.001	0.008
62407	1213671	160	0.005	0.160
62408	1213672	96	0.003	0.096
62409	1213673	39	0.001	0.039
62410	1213674	28	<0.001	0.028
62411 Rep	1213674	15	<0.001	0.015
62412	1213675	1541	0.045	1.541
62413	1213676	324	0.009	0.324
62414	1213677	39	0.001	0.039
62415	1213678	201	0.006	0.201
62416	1213679	25	<0.001	0.025
62417	1213680	1140	0.033	1.140
62418	1213681	27	<0.001	0.027
62419	1213682	30	<0.001	0.030
62420	1213683	15	<0.001	0.015
62421	1213684	478	0.014	0.478
62422 Dup	1213684	557	0.016	0.557
62423	1213685	22	<0.001	0.022
62424	1213686	1236	0.036	1.236
62425	1213687	85	0.002	0.085
62426	1213688	49	0.001	0.049
62427	1213689	120	0.003	0.120
62428	1213690	<5	<0.001	<0.005
62429	1213691	53	0.002	0.053
62430	1213692	39	0.001	0.039
62431	1213693	176	0.005	0.176
62432	1213694	21	<0.001	0.021
62433 Dup	1213694	20	<0.001	0.020
62434	1213695	7	<0.001	0.007
62435	1213696	5	<0.001	0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, March 20, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 03/06/2012
 Date Completed: 03/20/2012
 Job #: 201240685
 Reference: TL 12 239
 Sample #: 151

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
62436	1213697	6	<0.001	0.006
62437	1213698	7	<0.001	0.007
62438	1213699	12	<0.001	0.012
62439	1213700	250	0.007	0.250
62440	1213701	171	0.005	0.171
62441	1213702	73	0.002	0.073
62442	1213703	33	<0.001	0.033
62443	1213704	47	0.001	0.047
62444 Dup	1213704	39	0.001	0.039
62445	1213705	27	<0.001	0.027
62446	1213706	11	<0.001	0.011
62447	1213707	70	0.002	0.070
62448	1213708	72	0.002	0.072
62449	1213709	317	0.009	0.317
62450	1213710	<5	<0.001	<0.005
62451	1213711	179	0.005	0.179
62452	1213712	53	0.002	0.053
62453	1213713	50	0.001	0.050
62454	1213714	26	<0.001	0.026
62455 Dup	1213714	30	<0.001	0.030
62456	1213715	82	0.002	0.082
62457	1213716	101	0.003	0.101
62458	1213717	213	0.006	0.213
62459	1213718	31	<0.001	0.031
62460	1213719	102	0.003	0.102
62461	1213720	1200	0.035	1.200
62462	1213721	48	0.001	0.048
62463	1213722	21	<0.001	0.021
62464	1213723	48	0.001	0.048
62465	1213724	24	<0.001	0.024

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, March 20, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 03/06/2012
 Date Completed: 03/20/2012
 Job #: 201240685
 Reference: TL 12 239
 Sample #: 151

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
62466 Dup	1213724	45	0.001	0.045
62467	1213725	15	<0.001	0.015
62468	1213726	20	<0.001	0.020
62469	1213727	160	0.005	0.160
62470	1213728	16	<0.001	0.016
62471	1213729	40	0.001	0.040
62472	1213730	<5	<0.001	<0.005
62473	1213731	113	0.003	0.113
62474	1213732	58	0.002	0.058
62475	1213733	11	<0.001	0.011
62476	1213734	14	<0.001	0.014
62477 Rep	1213734	15	<0.001	0.015
62478	1213735	76	0.002	0.076
62479	1213736	64	0.002	0.064
62480	1213737	62	0.002	0.062
62481	1213738	12	<0.001	0.012
62482	1213739	10	<0.001	0.010
62483	1213740	1184	0.035	1.184
62484	1213741	11	<0.001	0.011
62485	1213742	41	0.001	0.041
62486	1213743	711	0.021	0.711
62487	1213744	76	0.002	0.076
62488 Dup	1213744	52	0.002	0.052
62489	1213745	17	<0.001	0.017
62490	1213746	50	0.001	0.050
62491	1213747	694	0.020	0.694
62492	1213748	61	0.002	0.061
62493	1213749	15	<0.001	0.015
62494	1213750	<5	<0.001	<0.005
62495	1213751	26	<0.001	0.026

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, March 20, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 03/06/2012
 Date Completed: 03/20/2012
 Job #: 201240685
 Reference: TL 12 239
 Sample #: 151

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
62496	1213752	14	<0.001	0.014
62497	1213753	765	0.022	0.765
62498	1213754	11	<0.001	0.011
62499 Dup	1213754	11	<0.001	0.011
62500	1213755	21	<0.001	0.021
62501	1213756	26	<0.001	0.026
62502	1213757	377	0.011	0.377
62503	1213758	238	0.007	0.238
62504	1213759	11	<0.001	0.011
62505	1213760	275	0.008	0.275
62506	1213761	18	<0.001	0.018
62507	1213762	81	0.002	0.081
62508	1213763	25	<0.001	0.025
62509	1213764	31	<0.001	0.031
62510 Dup	1213764	23	<0.001	0.023
62511	1213765	8	<0.001	0.008

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bac., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Monday, April 9, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 03/26/2012
 Date Completed: 04/09/2012
 Job #: 201240914
 Reference: TL 12 240
 Sample #: 149

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
81413	1213766	22	<0.001	0.022
81414	1213767	41	0.001	0.041
81415	1213768	38	0.001	0.038
81416	1213769	74	0.002	0.074
81417	1213770	<5	<0.001	<0.005
81418	1213771	13	<0.001	0.013
81419	1213772	363	0.011	0.363
81420	1213773	29	<0.001	0.029
81421	1213774	9	<0.001	0.009
81422	1213775	31	<0.001	0.031
81423 Dup	1213775	22	<0.001	0.022
81424	1213776	22	<0.001	0.022
81425	1213777	40	0.001	0.040
81426	1213778	57	0.002	0.057
81427	1213779	210	0.006	0.210
81428	1213780	4987	0.146	4.987
81429	1213781	66	0.002	0.066
81430	1213782	36	0.001	0.036
81431	1213783	72	0.002	0.072
81432	1213784	13	<0.001	0.013
81433	1213785	12	<0.001	0.012
81434 Dup	1213785	14	<0.001	0.014
81435	1213786	14	<0.001	0.014
81436	1213787	23	<0.001	0.023
81437	1213788	7	<0.001	0.007
81438	1213789	<5	<0.001	<0.005
81439	1213790	<5	<0.001	<0.005
81440	1213791	5	<0.001	0.005
81441	1213792	8	<0.001	0.008
81442	1213793	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Monday, April 9, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 03/26/2012
 Date Completed: 04/09/2012
 Job #: 201240914
 Reference: TL 12 240
 Sample #: 149

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
81443	1213794	7	<0.001	0.007
81444	1213795	71	0.002	0.071
81445 Dup	1213795	59	0.002	0.059
81446	1213796	70	0.002	0.070
81447	1213797	21	<0.001	0.021
81448	1213798	70	0.002	0.070
81449	1213799	77	0.002	0.077
81450	1213800	1343	0.039	1.343
81451	1213801	29	<0.001	0.029
81452	1213802	7	<0.001	0.007
81453	1213803	14	<0.001	0.014
81454	1213804	11	<0.001	0.011
81455	1213805	15	<0.001	0.015
81456 Dup	1213805	18	<0.001	0.018
81457	1213806	244	0.007	0.244
81458	1213807	37	0.001	0.037
81459	1213808	47	0.001	0.047
81460	1213809	23	<0.001	0.023
81461	1213810	<5	<0.001	<0.005
81462	1213811	17	<0.001	0.017
81463	1213812	34	<0.001	0.034
81464	1213813	19	<0.001	0.019
81465	1213814	20	<0.001	0.020
81466	1213815	71	0.002	0.071
81467 Dup	1213815	62	0.002	0.062
81468	1213816	49	0.001	0.049
81469	1213817	213	0.006	0.213
81470	1213818	230	0.007	0.230
81471	1213819	216	0.006	0.216
81472	1213820	251	0.007	0.251

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Monday, April 9, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 03/26/2012
 Date Completed: 04/09/2012
 Job #: 201240914
 Reference: TL 12 240
 Sample #: 149

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
81473	1213821	27	<0.001	0.027
81474	1213822	32	<0.001	0.032
81475	1213823	16	<0.001	0.016
81476	1213824	160	0.005	0.160
81477	1213825	441	0.013	0.441
81478 Rep	1213825	452	0.013	0.452
81479	1213826	516	0.015	0.516
81480	1213827	180	0.005	0.180
81481	1213828	197	0.006	0.197
81482	1213829	18	<0.001	0.018
81483	1213830	7	<0.001	0.007
81484	1213831	9	<0.001	0.009
81485	1213832	12	<0.001	0.012
81486	1213833	7	<0.001	0.007
81487	1213834	20	<0.001	0.020
81488	1213835	8	<0.001	0.008
81489 Dup	1213835	9	<0.001	0.009
81490	1213836	9	<0.001	0.009
81491	1213837	19	<0.001	0.019
81492	1213838	8	<0.001	0.008
81493	1213839	7	<0.001	0.007
81494	1213840	5135	0.150	5.135
81495	1213841	18	<0.001	0.018
81496	1213842	11	<0.001	0.011
81497	1213843	10	<0.001	0.010
81498	1213844	7	<0.001	0.007
81499	1213845	12	<0.001	0.012
81500 Dup	1213845	12	<0.001	0.012
81501	1213846	12	<0.001	0.012
81502	1213847	400	0.012	0.400

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Monday, April 9, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 03/26/2012
 Date Completed: 04/09/2012
 Job #: 201240914
 Reference: TL 12 240
 Sample #: 149

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
81503	1213848	37	0.001	0.037
81504	1213849	271	0.008	0.271
81505	1213850	8	<0.001	0.008
81506	1213851	19	<0.001	0.019
81507	1213852	29	<0.001	0.029
81508	1213853	17	<0.001	0.017
81509	1213854	28	<0.001	0.028
81510	1213855	41	0.001	0.041
81511 Dup	1213855	34	0.001	0.034
81512	1213856	56	0.002	0.056
81513	1213857	22	<0.001	0.022
81514	1213858	13	<0.001	0.013
81515	1213859	33	<0.001	0.033
81516	1213860	1201	0.035	1.201
81517	1213861	618	0.018	0.618
81518	1213862	99	0.003	0.099
81519	1213863	18	<0.001	0.018
81520	1213864	27	<0.001	0.027
81521	1213865	83	0.002	0.083
81522 Dup	1213865	25	<0.001	0.025
81523	1213866	22	<0.001	0.022
81524	1213867	33	<0.001	0.033
81525	1213868	30	<0.001	0.030
81526	1213869	22977	0.670	22.977
81527	1213870	8	<0.001	0.008
81528	1213871	266	0.008	0.266
81529	1213872	28	<0.001	0.028
81530	1213873	47	0.001	0.047
81531	1213874	30	<0.001	0.030
81532	1213875	23	<0.001	0.023

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Monday, April 9, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 03/26/2012
 Date Completed: 04/09/2012
 Job #: 201240914
 Reference: TL 12 240
 Sample #: 149

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
81533 Dup	1213875	22	<0.001	0.022
81534	1213876	24	<0.001	0.024
81535	1213877	384	0.011	0.384
81536	1213878	39	0.001	0.039
81537	1213879	140	0.004	0.140
81538	1213880	248	0.007	0.248
81539	1213881	84	0.002	0.084
81540	1213882	156	0.005	0.156
81541	1213883	165	0.005	0.165
81542	1213884	50	0.001	0.050
81543	1213885	16	<0.001	0.016
81544 Rep	1213885	15	<0.001	0.015
81545	1213886	17	<0.001	0.017
81546	1213887	51	0.001	0.051
81547	1213888	50	0.001	0.050
81548	1213889	<5	<0.001	<0.005
81549	1213890	<5	<0.001	<0.005
81550	1213891	<5	<0.001	<0.005
81551	1213892	<5	<0.001	<0.005
81552	1213893	<5	<0.001	<0.005
81553	1213894	17	<0.001	0.017
81554	1213895	<5	<0.001	<0.005
81555 Dup	1213895	<5	<0.001	<0.005
81556	1213896	<5	<0.001	<0.005
81557	1213897	18	<0.001	0.018
81558	1213898	7	<0.001	0.007
81559	1213899	<5	<0.001	<0.005
81560	1213900	5031	0.147	5.031
81561	1213901	<5	<0.001	<0.005
81562	1213902	8	<0.001	0.008

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Monday, April 9, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 03/26/2012
 Date Completed: 04/09/2012
 Job #: 201240914
 Reference: TL 12 240
 Sample #: 149

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
81563	1213903	21	<0.001	0.021
81564	1213904	495	0.014	0.495
81565	1213905	863	0.025	0.863
81566 Dup	1213905	901	0.026	0.901
81567	1213906	77	0.002	0.077
81568	1213907	21	<0.001	0.021
81569	1213908	20	<0.001	0.020
81570	1213909	10	<0.001	0.010
81571	1213910	<5	<0.001	<0.005
81572	1213911	22	<0.001	0.022
81573	1213912	83	0.002	0.083
81574	1213913	41	0.001	0.041
81575	1213914	61	0.002	0.061

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Monday, April 9, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 03/27/2012
 Date Completed: 04/09/2012
 Job #: 201240930
 Reference: TL 12 241
 Sample #: 179

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
84171	1213915	39	0.001	0.039
84172	1213916	39	0.001	0.039
84173	1213917	802	0.023	0.802
84174	1213918	25	<0.001	0.025
84175	1213919	11	<0.001	0.011
84176	1213920	1185	0.035	1.185
84177	1213921	147	0.004	0.147
84178	1213922	144	0.004	0.144
84179	1213923	129	0.004	0.129
84180	1213924	183	0.005	0.183
84181 Dup	1213924	177	0.005	0.177
84182	1213925	67	0.002	0.067
84183	1213926	209	0.006	0.209
84184	1213927	462	0.013	0.462
84185	1213928	364	0.011	0.364
84186	1213929	329	0.010	0.329
84187	1213930	6	<0.001	0.006
84188	1213931	260	0.008	0.260
84189	1213932	907	0.026	0.907
84190	1213933	301	0.009	0.301
84191	1213934	283	0.008	0.283
84192 Dup	1213934	269	0.008	0.269
84193	1213935	873	0.025	0.873
84194	1213936	831	0.024	0.831
84195	1213937	235	0.007	0.235
84196	1213938	539	0.016	0.539
84197	1213939	86	0.003	0.086
84198	1213940	237	0.007	0.237
84199	1213941	33	<0.001	0.033
84200	1213942	39	0.001	0.039

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Monday, April 9, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 03/27/2012
 Date Completed: 04/09/2012
 Job #: 201240930
 Reference: TL 12 241
 Sample #: 179

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
84201	1213943	262	0.008	0.262
84202	1213944	81	0.002	0.081
84203 Dup	1213944	70	0.002	0.070
84204	1213945	34	<0.001	0.034
84205	1213946	50	0.001	0.050
84206	1213947	14	<0.001	0.014
84207	1213948	12	<0.001	0.012
84208	1213949	13	<0.001	0.013
84209	1213950	7	<0.001	0.007
84210	1213951	11	<0.001	0.011
84211	1213952	11	<0.001	0.011
84212	1213953	81	0.002	0.081
84213	1213954	99	0.003	0.099
84214 Dup	1213954	113	0.003	0.113
84215	1213955	38	0.001	0.038
84216	1213956	34	<0.001	0.034
84217	1213957	178	0.005	0.178
84218	1213958	61	0.002	0.061
84219	1213959	22	<0.001	0.022
84220	1213960	5091	0.149	5.091
84221	1213961	33	<0.001	0.033
84222	1213962	42	0.001	0.042
84223	1213963	21	<0.001	0.021
84224	1213964	28	<0.001	0.028
84225 Dup	1213964	21	<0.001	0.021
84226	1213965	17	<0.001	0.017
84227	1213966	19	<0.001	0.019
84228	1213967	100	0.003	0.100
84229	1213968	45	0.001	0.045
84230	1213969	16	<0.001	0.016

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Monday, April 9, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 03/27/2012
 Date Completed: 04/09/2012
 Job #: 201240930
 Reference: TL 12 241
 Sample #: 179

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
84231	1213970	7	<0.001	0.007
84232	1213971	14	<0.001	0.014
84233	1213972	16	<0.001	0.016
84234	1213973	20	<0.001	0.020
84235	1213974	33	<0.001	0.033
84236 Rep	1213974	33	<0.001	0.033
84237	1213975	20	<0.001	0.020
84238	1213976	20	<0.001	0.020
84239	1213977	35	0.001	0.035
84240	1213978	110	0.003	0.110
84241	1213979	183	0.005	0.183
84242	1213980	1072	0.031	1.072
84243	1213981	202	0.006	0.202
84244	1213982	24	<0.001	0.024
84245	1213983	13	<0.001	0.013
84246	1213984	11	<0.001	0.011
84247 Dup	1213984	12	<0.001	0.012
84248	1213985	12	<0.001	0.012
84249	1213986	16	<0.001	0.016
84250	1213987	61	0.002	0.061
84251	1213988	9	<0.001	0.009
84252	1213989	6	<0.001	0.006
84253	1213990	<5	<0.001	<0.005
84254	1213991	8	<0.001	0.008
84255	1213992	19	<0.001	0.019
84256	1213993	7	<0.001	0.007
84257	1213994	8	<0.001	0.008
84258 Dup	1213994	5	<0.001	0.005
84259	1213995	9	<0.001	0.009
84260	1213996	12	<0.001	0.012

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Monday, April 9, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 03/27/2012
 Date Completed: 04/09/2012
 Job #: 201240930
 Reference: TL 12 241
 Sample #: 179

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
84261	1213997	165	0.005	0.165
84262	1213998	113	0.003	0.113
84263	1213999	18	<0.001	0.018
84264	1214000	222	0.006	0.222
84265	1185151	7	<0.001	0.007
84266	1185152	18	<0.001	0.018
84267	1185153	18	<0.001	0.018
84268	1185154	11	<0.001	0.011
84269 Dup	1185154	14	<0.001	0.014
84270	1185155	9	<0.001	0.009
84271	1185156	<5	<0.001	<0.005
84272	1185157	27	<0.001	0.027
84273	1185158	21	<0.001	0.021
84274	1185159	24	<0.001	0.024
84275	1185160	<5	<0.001	<0.005
84276	1185161	27	<0.001	0.027
84277	1185162	20	<0.001	0.020
84278	1185163	30	<0.001	0.030
84279	1185164	23	<0.001	0.023
84280 Dup	1185164	24	<0.001	0.024
84281	1185165	22	<0.001	0.022
84282	1185166	788	0.023	0.788
84283	1185167	58	0.002	0.058
84284	1185168	223	0.006	0.223
84285	1185169	74	0.002	0.074
84286	1185170	4841	0.141	4.841
84287	1185171	356	0.010	0.356
84288	1185172	143	0.004	0.143
84289	1185173	127	0.004	0.127
84290	1185174	16	<0.001	0.016

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Monday, April 9, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 03/27/2012
 Date Completed: 04/09/2012
 Job #: 201240930
 Reference: TL 12 241
 Sample #: 179

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
84291 Dup	1185174	42	0.001	0.042
84292	1185175	14	<0.001	0.014
84293	1185176	16	<0.001	0.016
84294	1185177	10	<0.001	0.010
84295	1185178	10	<0.001	0.010
84296	1185179	9	<0.001	0.009
84297	1185180	<5	<0.001	<0.005
84298	1185181	20	<0.001	0.020
84299	1185182	17	<0.001	0.017
84300	1185183	14	<0.001	0.014
84301	1185184	7	<0.001	0.007
84302 Rep	1185184	<5	<0.001	<0.005
84303	1185185	6	<0.001	0.006
84304	1185186	7	<0.001	0.007
84305	1185187	<5	<0.001	<0.005
84306	1185188	<5	<0.001	<0.005
84307	1185189	9	<0.001	0.009
84308	1185190	1023	0.030	1.023
84309	1185191	16	<0.001	0.016
84310	1185192	<5	<0.001	<0.005
84311	1185193	<5	<0.001	<0.005
84312	1185194	8	<0.001	0.008
84313 Dup	1185194	<5	<0.001	<0.005
84314	1185195	24	<0.001	0.024
84315	1185196	16	<0.001	0.016
84316	1185197	20	<0.001	0.020
84317	1185198	126	0.004	0.126
84318	1185199	10	<0.001	0.010
84319	1185200	<5	<0.001	<0.005
84320	1185201	48	0.001	0.048

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Monday, April 9, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 03/27/2012
 Date Completed: 04/09/2012
 Job #: 201240930
 Reference: TL 12 241
 Sample #: 179

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
84321	1185202	440	0.013	0.440
84322	1185203	208	0.006	0.208
84323	1185204	28	<0.001	0.028
84324 Dup	1185204	30	<0.001	0.030
84325	1185205	110	0.003	0.110
84326	1185206	322	0.009	0.322
84327	1185207	80	0.002	0.080
84328	1185208	218	0.006	0.218
84329	1185209	33	<0.001	0.033
84330	1185210	221	0.006	0.221
84331	1185211	179	0.005	0.179
84332	1185212	31	<0.001	0.031
84333	1185213	338	0.010	0.338
84334	1185214	7107	0.207	7.107
84335 Dup	1185214	9226	0.269	9.226
84336	1185215	232	0.007	0.232
84337	1185216	121	0.004	0.121
84338	1185217	112	0.003	0.112
84339	1185218	76	0.002	0.076
84340	1185219	189	0.006	0.189
84341	1185220	9	<0.001	0.009
84342	1185221	76	0.002	0.076
84343	1185222	58	0.002	0.058
84344	1185223	91	0.003	0.091
84345	1185224	217	0.006	0.217
84346 Dup	1185224	187	0.005	0.187
84347	1185225	20	<0.001	0.020
84348	1185226	15	<0.001	0.015
84349	1185227	20	<0.001	0.020
84350	1185228	260	0.008	0.260

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Monday, April 9, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 03/27/2012
 Date Completed: 04/09/2012
 Job #: 201240930
 Reference: TL 12 241
 Sample #: 179

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
84351	1185229	13	<0.001	0.013
84352	1185230	4931	0.144	4.931
84353	1185231	78	0.002	0.078
84354	1185232	15	<0.001	0.015
84355	1185233	128	0.004	0.128
84356	1185234	15	<0.001	0.015
84357 Dup	1185234	19	<0.001	0.019
84358	1185235	83	0.002	0.083
84359	1185236	54	0.002	0.054
84360	1185237	36	0.001	0.036
84361	1185238	33	<0.001	0.033
84362	1185239	662	0.019	0.662
84363	1185240	<5	<0.001	<0.005
84364	1185241	18	<0.001	0.018
84365	1185242	138	0.004	0.138
84366	1185243	108	0.003	0.108

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bac., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Monday, April 9, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 03/29/2012
 Date Completed: 04/09/2012
 Job #: 201240965
 Reference: TL 12 242
 Sample #: 138

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
86024	1185244	50	0.001	0.050
86025	1185245	34	0.001	0.034
86026	1185246	36	0.001	0.036
86027	1185247	69	0.002	0.069
86028	1185248	213	0.006	0.213
86029	1185249	65	0.002	0.065
86030	1185250	1176	0.034	1.176
86031	1185251	14	<0.001	0.014
86032	1185252	67	0.002	0.067
86033	1185253	50	0.001	0.050
86034 Dup	1185253	59	0.002	0.059
86035	1185254	15	<0.001	0.015
86036	1185255	50	0.001	0.050
86037	1185256	48	0.001	0.048
86038	1185257	34	<0.001	0.034
86039	1185258	54	0.002	0.054
86040	1185259	14	<0.001	0.014
86041	1185260	<5	<0.001	<0.005
86042	1185261	14	<0.001	0.014
86043	1185262	17	<0.001	0.017
86044	1185263	24	<0.001	0.024
86045 Dup	1185263	21	<0.001	0.021
86046	1185264	18	<0.001	0.018
86047	1185265	96	0.003	0.096
86048	1185266	104	0.003	0.104
86049	1185267	23	<0.001	0.023
86050	1185268	47	0.001	0.047
86051	1185269	21	<0.001	0.021
86052	1185270	258	0.008	0.258
86053	1185271	18	<0.001	0.018

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Monday, April 9, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 03/29/2012
 Date Completed: 04/09/2012
 Job #: 201240965
 Reference: TL 12 242
 Sample #: 138

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
86054	1185272	15	<0.001	0.015
86055	1185273	11	<0.001	0.011
86056 Dup	1185273	15	<0.001	0.015
86057	1185274	20	<0.001	0.020
86058	1185275	13	<0.001	0.013
86059	1185276	16	<0.001	0.016
86060	1185277	15	<0.001	0.015
86061	1185278	<5	<0.001	<0.005
86062	1185279	8	<0.001	0.008
86063	1185280	6	<0.001	0.006
86064	1185281	22	<0.001	0.022
86065	1185282	41	0.001	0.041
86066	1185283	10	<0.001	0.010
86067 Dup	1185283	9	<0.001	0.009
86068	1185284	20	<0.001	0.020
86069	1185285	36	0.001	0.036
86070	1185286	89	0.003	0.089
86071	1185287	34	<0.001	0.034
86072	1185288	31	<0.001	0.031
86073	1185289	45	0.001	0.045
86074	1185290	5306	0.155	5.306
86075	1185291	37	0.001	0.037
86076	1185292	127	0.004	0.127
86077	1185293	44	0.001	0.044
86078 Dup	1185293	49	0.001	0.049
86079	1185294	16	<0.001	0.016
86080	1185295	17	<0.001	0.017
86081	1185296	17	<0.001	0.017
86082	1185297	28	<0.001	0.028
86083	1185298	68	0.002	0.068

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Monday, April 9, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 03/29/2012
 Date Completed: 04/09/2012
 Job #: 201240965
 Reference: TL 12 242
 Sample #: 138

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
86084	1185299	<5	<0.001	<0.005
86085	1185300	<5	<0.001	<0.005
86086	1185301	8	<0.001	0.008
86087	1185302	9	<0.001	0.009
86088	1185303	10	<0.001	0.010
86089 Rep	1185303	12	<0.001	0.012
86090	1185304	22	<0.001	0.022
86091	1185305	13	<0.001	0.013
86092	1185306	12	<0.001	0.012
86093	1185307	11	<0.001	0.011
86094	1185308	28	<0.001	0.028
86095	1185309	44	0.001	0.044
86096	1185310	1266	0.037	1.266
86097	1185311	11	<0.001	0.011
86098	1185312	<5	<0.001	<0.005
86099	1185313	16	<0.001	0.016
86100 Dup	1185313	17	<0.001	0.017
86101	1185314	175	0.005	0.175
86102	1185315	108	0.003	0.108
86103	1185316	88	0.003	0.088
86104	1185317	37	0.001	0.037
86105	1185318	545	0.016	0.545
86106	1185319	707	0.021	0.707
86107	1185320	<5	<0.001	<0.005
86108	1185321	706	0.021	0.706
86109	1185322	1158	0.034	1.158
86110	1185323	17	<0.001	0.017
86111 Dup	1185323	14	<0.001	0.014
86112	1185324	<5	<0.001	<0.005
86113	1185325	6	<0.001	0.006

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Monday, April 9, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 03/29/2012
 Date Completed: 04/09/2012
 Job #: 201240965
 Reference: TL 12 242
 Sample #: 138

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
86114	1185326	9	<0.001	0.009
86115	1185327	43	0.001	0.043
86116	1185328	150	0.004	0.150
86117	1185329	640	0.019	0.640
86118	1185330	221	0.006	0.221
86119	1185331	455	0.013	0.455
86120	1185332	227	0.007	0.227
86121	1185333	264	0.008	0.264
86122 Dup	1185333	344	0.010	0.344
86123	1185334	148	0.004	0.148
86124	1185335	197	0.006	0.197
86125	1185336	172	0.005	0.172
86126	1185337	256	0.007	0.256
86127	1185338	128	0.004	0.128
86128	1185339	192	0.006	0.192
86129	1185340	7	<0.001	0.007
86130	1185341	624	0.018	0.624
86131	1185342	464	0.014	0.464
86132	1185343	349	0.010	0.349
86133 Dup	1185343	290	0.008	0.290
86134	1185344	173	0.005	0.173
86135	1185345	51	0.001	0.051
86136	1185346	293	0.009	0.293
86137	1185347	50	0.001	0.050
86138	1185348	24	<0.001	0.024
86139	1185349	43	0.001	0.043
86140	1185350	5079	0.148	5.079
86141	1185351	16	<0.001	0.016
86142	1185352	12	<0.001	0.012
86143	1185353	66	0.002	0.066

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Monday, April 9, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 03/29/2012
 Date Completed: 04/09/2012
 Job #: 201240965
 Reference: TL 12 242
 Sample #: 138

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
86144 Dup	1185353	58	0.002	0.058
86145	1185354	24	<0.001	0.024
86146	1185355	27	<0.001	0.027
86147	1185356	32	<0.001	0.032
86148	1185357	38	0.001	0.038
86149	1185358	17	<0.001	0.017
86150	1185359	13	<0.001	0.013
86151	1185360	11	<0.001	0.011
86152	1185361	10	<0.001	0.010
86153	1185362	14	<0.001	0.014
86154	1185363	22	<0.001	0.022
86155 Rep	1185363	19	<0.001	0.019
86156	1185364	18	<0.001	0.018
86157	1185365	16	<0.001	0.016
86158	1185366	11	<0.001	0.011
86159	1185367	14	<0.001	0.014
86160	1185368	22	<0.001	0.022
86161	1185369	21	<0.001	0.021
86162	1185370	1382	0.040	1.382
86163	1185371	59	0.002	0.059
86164	1185372	52	0.002	0.052
86165	1185373	73	0.002	0.073
86166 Dup	1185373	144	0.004	0.144
86167	1185374	199	0.006	0.199
86168	1185375	36	0.001	0.036
86169	1185376	39	0.001	0.039
86170	1185377	51	0.001	0.051
86171	1185378	33	<0.001	0.033
86172	1185379	17	<0.001	0.017
86173	1185380	9	<0.001	0.009

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Monday, April 9, 2012

Certificate of Analysis

Treasury Metals Inc
Exchange Tower 130 King St Suite 3680
Toronto, On, CAN
M5X 1B1
Ph#: (416) 599-4133
Fax#: (416) 599-4959
Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 03/29/2012
Date Completed: 04/09/2012
Job #: 201240965
Reference: TL 12 242
Sample #: 138

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
86174	1185381	7	<0.001	0.007

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
The Certificate of Analysis should not be reproduced except in full,
without the written approval of the laboratory

Tuesday, May 22, 2012

Certificate of Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 04/10/2012
 Date Completed: 04/24/2012
 Job #: 201241092
 Reference: TL 12 243
 Sample #: 209

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
95811	1185382	0.035	2	2.52	34	58	3	28	0.99	15	37	106	126	12.51	<0.01	1	1.07	1249	<1	59	282	71	8.99	5	7	<10	114	1753	<2	60	21	11	1460
95812	1185383	0.040	1	1.46	200	33	3	46	0.78	15	49	19	152	17.39	<0.01	<1	0.48	846	<1	61	253	53	>10.00	<5	6	<10	98	1065	4	31	<10	5	315
95813	1185384	0.086	1	2.64	12	303	<2	8	1.14	<4	9	13	12	2.01	<0.01	5	0.99	736	<1	10	456	15	1.76	<5	<5	<10	255	1729	3	32	<10	6	450
95814	1185385	0.347	3	3.10	8	377	<2	3	1.58	<4	7	13	36	1.55	0.19	3	0.75	719	<1	4	398	16	1.69	<5	10	<10	363	1541	3	28	52	5	262
95815	1185386	0.061	2	1.88	7	208	2	10	1.07	<4	6	11	28	1.39	0.15	<1	0.44	356	<1	5	329	15	1.54	<5	10	<10	275	1133	2	19	<10	5	150
95816	1185387	0.135	1	2.37	8	309	<2	9	1.14	<4	7	11	8	1.59	0.13	4	0.94	567	<1	6	383	18	1.62	<5	<5	<10	366	1334	2	28	<10	4	257
95817	1185388	0.183	2	2.43	12	417	2	2	1.25	5	7	9	115	1.68	0.36	4	0.73	605	<1	5	391	105	1.90	<5	7	<10	453	1388	<2	30	17	4	1220
95818	1185389	0.484	2	2.74	11	521	2	12	1.12	<4	7	8	46	1.83	0.57	5	0.93	711	<1	6	424	29	1.90	<5	9	<10	315	1602	<2	33	<10	4	624
95819	1185390	0.254	<1	<0.01	408	>5000	<2	10	0.76	<4	8	13	31	2.81	<0.01	<1	0.18	<100	4	9	<100	23	0.88	17	6	<10	118	711	8	15	43	6	36
95820	1185391	1.989	7	1.48	13	451	<2	10	0.58	<4	6	15	203	1.67	<0.01	4	0.95	646	<1	5	385	11	1.71	<5	5	<10	170	1223	2	28	<10	5	303
95821D	1185391	2.028	8	1.22	8	335	<2	11	0.75	<4	6	16	204	1.54	0.06	4	0.84	622	<1	6	367	14	1.67	<5	6	<10	227	1228	<2	28	<10	4	290
95822	1185392	4.536	16	1.87	10	526	<2	15	0.30	13	8	11	468	2.18	<0.01	10	1.16	768	<1	7	501	17	2.46	<5	9	<10	134	1702	<2	32	41	4	3475
95823	1185393	0.217	2	0.93	11	434	2	7	0.64	<4	8	31	33	1.81	<0.01	4	0.90	785	<1	26	422	41	1.68	<5	6	<10	131	1364	<2	33	<10	5	172
95824	1185394	0.076	2	2.24	13	485	<2	15	0.88	<4	9	14	20	1.93	<0.01	6	1.00	644	<1	8	498	18	2.13	<5	6	<10	287	1632	<2	37	<10	5	168
95825	1185395	0.111	1	3.18	12	408	<2	12	1.73	<4	11	19	25	2.13	0.19	6	1.30	936	<1	10	588	15	1.67	<5	7	<10	333	2281	5	44	<10	6	115
95826	1185396	0.106	1	3.41	13	450	<2	11	1.93	<4	10	19	30	2.12	0.27	8	1.30	992	<1	12	581	17	1.62	5	8	<10	376	2239	6	45	<10	6	122
95827	1185397	0.212	2	3.32	4	368	2	<1	1.27	6	9	14	376	1.97	0.43	5	1.12	618	<1	8	496	11	1.02	<5	5	<10	406	2217	4	39	17	6	1368
95828	1185398	0.022	<1	2.76	7	475	<2	9	1.46	<4	9	16	20	1.91	0.45	5	0.80	444	<1	9	507	13	0.87	<5	7	<10	437	2370	3	40	<10	5	93
95829	1185399	0.019	<1	2.82	5	449	<2	27	1.70	<4	10	19	15	1.88	0.32	3	0.64	415	<1	8	506	16	1.12	<5	7	<10	349	2360	2	41	<10	5	81
95830	1185400	<0.005	<1	2.38	7	271	<2	4	1.26	<4	11	25	20	2.20	0.20	3	0.85	416	<1	17	478	12	0.40	<5	7	<10	175	1700	5	71	20	12	35

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, May 22, 2012

Certificate of Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 04/10/2012
 Date Completed: 04/24/2012
 Job #: 201241092
 Reference: TL 12 243
 Sample #: 209

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
95831	1185401	0.024	<1	1.10	6	323	<2	41	0.96	<4	10	17	20	2.00	0.03	5	0.82	598	<1	9	544	15	1.15	<5	10	<10	149	2307	3	39	<10	6	96
95832D	1185401	0.020	<1	1.09	6	403	<2	13	1.25	<4	10	16	19	1.91	<0.01	3	0.70	589	<1	8	532	18	1.11	<5	5	<10	250	2358	<2	39	<10	4	88
95833	1185402	0.033	<1	1.49	7	339	<2	3	0.97	5	9	18	47	2.07	<0.01	6	0.92	686	<1	7	532	14	1.54	<5	7	<10	196	1920	3	37	15	5	874
95834	1185403	0.146	2	2.61	13	422	<2	19	0.92	12	9	12	82	2.12	<0.01	10	1.24	827	<1	9	527	28	1.47	<5	7	<10	264	1778	3	37	33	5	2820
95835	1185404	0.035	<1	2.82	9	435	<2	<1	1.03	<4	9	15	14	2.08	<0.01	8	1.18	868	<1	6	562	18	1.17	<5	8	<10	235	1831	2	38	<10	6	341
95836	1185405	0.805	<1	2.76	9	421	<2	16	1.33	<4	8	20	14	1.91	0.19	7	0.90	664	<1	7	526	17	0.97	<5	8	<10	307	1735	2	37	<10	5	130
95837	1185406	0.067	<1	2.86	6	395	<2	16	1.25	<4	9	15	36	1.97	0.20	9	1.03	743	<1	10	533	14	1.04	<5	8	<10	212	1887	<2	37	<10	6	115
95838	1185407	0.020	<1	3.42	8	475	<2	16	1.15	<4	9	16	11	2.07	0.16	12	1.22	815	<1	8	540	17	1.16	<5	<5	<10	288	1763	3	41	<10	5	219
95839	1185408	0.040	<1	3.42	10	431	<2	13	1.17	<4	8	15	8	1.96	0.34	8	1.37	868	<1	8	512	15	1.14	<5	6	<10	311	1391	8	36	<10	5	446
95840	1185409	0.048	<1	3.16	13	548	2	10	0.94	4	9	12	21	2.02	0.31	10	1.27	840	<1	8	528	18	1.29	<5	8	<10	266	1570	5	37	<10	5	681
95841	1185410	4.966	1	2.45	319	1175	<2	12	1.81	<4	11	91	69	2.75	0.22	7	1.01	385	5	37	663	26	1.14	28	8	<10	144	1344	2	99	<10	11	197
95842	1185411	0.031	<1	2.44	23	392	<2	15	1.07	8	9	14	88	1.95	<0.01	6	0.99	731	<1	9	468	26	1.37	<5	6	<10	248	1447	5	36	24	5	2119
95843D	1185411	0.028	<1	2.47	15	387	<2	4	0.93	9	10	14	98	2.13	<0.01	7	1.13	839	<1	8	546	22	1.47	<5	9	<10	202	1660	6	37	29	6	2434
95844	1185412	0.041	4	0.99	14	374	<2	10	0.85	6	10	18	97	2.34	<0.01	7	1.22	959	<1	11	602	1222	1.66	<5	7	<10	139	1914	3	40	18	6	1384
95845	1185413	0.015	<1	1.43	12	416	<2	<1	0.87	4	10	13	25	2.10	<0.01	8	0.92	808	<1	10	523	353	1.63	<5	6	<10	148	1785	2	38	11	5	695
95846	1185414	0.019	<1	2.17	12	462	<2	13	1.26	4	10	36	37	2.13	<0.01	6	1.02	946	<1	12	581	85	1.42	<5	7	<10	226	1924	<2	40	<10	5	695
95847	1185415	0.015	<1	1.46	7	315	<2	33	1.04	14	9	12	8	2.29	<0.01	13	1.04	596	<1	5	563	28	1.35	<5	6	<10	126	2218	5	43	31	6	2572
95848	1185416	<0.005	<1	1.79	10	337	<2	9	1.09	19	9	9	7	2.40	<0.01	12	1.08	599	<1	9	579	29	1.61	<5	6	<10	128	2248	7	44	47	6	3829
95849	1185417	0.016	<1	1.87	9	435	2	16	1.83	<4	9	10	20	2.07	<0.01	22	0.80	534	<1	7	549	29	1.15	<5	6	<10	312	2204	<2	49	<10	4	101
95850	1185418	0.055	<1	2.12	10	320	2	16	2.53	52	14	13	132	3.30	<0.01	19	1.21	752	<1	8	583	26	2.90	<5	<5	<10	279	2578	2	42	159	5	15733

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, May 22, 2012

Certificate of Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 04/10/2012
 Date Completed: 04/24/2012
 Job #: 201241092
 Reference: TL 12 243
 Sample #: 209

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
95851	1185419	0.035	1	1.13	7	426	2	9	1.26	<4	10	29	74	2.13	0.04	11	0.54	664	<1	9	467	179	1.15	<5	9	<10	247	2252	<2	46	<10	3	342
95852	1185420	<0.005	<1	0.92	5	353	2	9	1.32	<4	12	28	20	2.19	0.07	5	0.62	441	<1	20	448	16	0.45	<5	6	<10	227	2068	<2	76	25	7	46
95853	1185421	0.048	<1	1.95	6	444	<2	7	1.00	<4	11	19	49	1.98	<0.01	13	0.50	474	<1	9	459	59	1.00	<5	7	<10	212	2151	<2	44	<10	4	211
95854D	1185421	0.063	<1	1.19	6	489	<2	14	0.97	<4	11	21	49	1.90	<0.01	14	0.44	503	<1	10	443	64	1.01	<5	8	<10	214	2334	5	46	<10	3	209
95855	1185422	0.028	<1	2.14	5	486	2	14	1.03	<4	11	38	32	2.27	<0.01	14	0.68	621	<1	12	530	34	0.96	<5	7	<10	172	2271	<2	48	<10	5	186
95856	1185423	0.030	<1	3.09	8	429	<2	3	1.32	<4	10	26	21	2.06	0.17	14	0.76	549	<1	10	498	24	0.97	<5	10	<10	163	1986	<2	43	<10	6	92
95857	1185424	0.015	<1	3.05	10	354	<2	9	1.14	<4	7	31	17	1.59	0.10	12	0.83	485	<1	8	502	28	1.00	<5	<5	<10	163	1462	4	35	<10	5	75
95858	1185425	<0.005	<1	3.22	8	486	2	22	0.66	<4	9	18	9	0.72	0.19	9	0.31	128	<1	8	486	23	0.66	<5	10	<10	162	1575	<2	34	<10	4	45
95859	1185426	0.005	<1	3.66	7	416	2	17	0.82	<4	6	14	8	0.69	0.16	8	0.36	126	<1	10	499	16	0.58	<5	9	<10	169	1382	<2	33	<10	5	23
95860	1185427	<0.005	<1	3.35	4	430	2	10	1.06	<4	6	19	10	0.76	0.29	9	0.34	147	<1	6	499	13	0.56	<5	7	<10	207	1365	<2	34	<10	4	22
95861	1185428	<0.005	<1	2.69	6	415	2	7	1.13	<4	7	22	14	0.82	0.04	8	0.31	153	<1	8	481	19	0.61	<5	<5	<10	227	1333	<2	34	<10	4	31
95862	1185429	0.010	<1	1.31	4	473	2	5	1.30	<4	6	25	14	0.91	0.05	10	0.27	180	<1	7	489	14	0.46	<5	10	<10	286	1623	<2	41	<10	3	31
95863	1185430	1.490	1	1.22	21	497	<2	24	1.30	4	15	50	545	3.48	<0.01	5	0.78	571	21	31	594	72	0.89	5	9	<10	227	1991	<2	108	28	8	101
95864	1185431	<0.005	<1	1.18	8	457	2	12	1.59	<4	10	40	32	1.40	0.12	11	0.34	233	<1	15	417	17	0.74	<5	6	<10	276	1685	3	45	<10	4	51
95865D	1185431	0.022	<1	1.73	4	340	<2	8	1.14	<4	10	40	27	1.41	0.04	9	0.42	227	<1	15	461	15	0.70	<5	7	<10	193	1628	<2	41	<10	5	51
95866	1185432	0.019	<1	1.18	12	516	2	10	1.44	<4	11	28	17	0.96	0.05	9	0.36	215	<1	13	488	19	0.65	<5	8	<10	272	1770	<2	43	<10	3	51
95867	1185433	0.016	<1	2.18	16	586	2	5	0.85	<4	12	17	10	0.79	<0.01	13	0.37	190	<1	9	599	24	0.79	<5	6	<10	209	2098	2	46	<10	4	34
95868	1185434	0.039	<1	3.01	8	605	2	15	1.03	<4	10	26	12	0.70	0.08	12	0.39	157	<1	7	514	19	0.61	<5	12	<10	222	1938	<2	40	<10	4	35
95869	1185435	0.017	<1	2.70	6	414	<2	33	0.97	<4	7	17	10	0.66	<0.01	11	0.57	213	<1	6	349	18	0.62	<5	10	<10	181	1287	2	24	<10	3	33
95870	1185436	0.006	<1	2.45	7	468	2	3	1.10	<4	7	14	10	0.67	0.34	11	0.59	225	<1	7	337	18	0.57	<5	7	<10	212	1317	3	25	<10	3	37

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, May 22, 2012


Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/10/2012
 Date Completed: 04/24/2012
 Job #: 201241092
 Reference: TL 12 243
 Sample #: 209

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
95871	1185437	0.006	<1	1.40	7	388	2	11	0.86	<4	5	9	37	0.52	0.41	7	0.36	154	<1	5	302	15	0.58	<5	6	<10	194	1190	3	23	<10	3	14
95872	1185438	0.019	<1	3.69	9	454	<2	<1	0.94	<4	6	10	12	0.50	0.37	6	0.30	100	<1	6	331	13	0.67	<5	9	<10	232	1200	<2	22	<10	3	23
95873	1185439	0.014	<1	2.85	8	407	<2	14	1.01	<4	5	21	3	0.52	0.13	10	0.36	139	<1	4	348	16	0.53	<5	5	<10	249	1359	2	25	<10	3	11
95874	1185440	<0.005	<1	1.42	8	343	<2	1	1.38	<4	12	27	20	2.28	0.05	6	0.69	442	<1	18	461	13	0.49	<5	8	<10	223	1934	<2	77	23	8	39
95875	1185441	<0.005	<1	1.39	10	495	<2	<1	1.36	<4	7	12	9	0.68	0.14	7	0.32	203	<1	6	290	14	0.65	<5	9	<10	265	1425	3	26	<10	2	18
95876R	1185441	0.009	<1	1.07	9	548	<2	9	1.41	<4	7	29	10	0.77	0.13	9	0.27	224	<1	8	295	13	0.68	<5	9	<10	282	1543	2	28	<10	2	18
95877	1185442	<0.005	<1	0.99	9	454	3	23	1.23	<4	5	13	5	0.63	<0.01	8	0.28	187	<1	4	272	14	0.69	<5	8	<10	259	1362	<2	27	<10	3	20
95878	1185443	0.031	<1	1.25	9	457	2	5	1.42	<4	6	13	31	0.77	0.09	8	0.29	215	<1	5	296	21	0.86	<5	6	<10	257	1320	3	26	<10	2	136
95879	1185444	<0.005	<1	1.96	12	479	2	8	1.21	<4	4	11	10	0.60	0.13	7	0.23	161	<1	4	312	20	0.69	<5	7	<10	236	1350	<2	25	<10	2	25
95880	1185445	0.016	<1	3.33	11	509	<2	6	1.20	<4	4	12	6	0.68	0.03	10	0.41	240	<1	3	326	24	0.73	<5	9	<10	224	1405	<2	25	<10	3	32
95881	1185446	0.014	<1	3.42	8	359	2	10	1.01	<4	4	16	14	0.81	0.25	10	0.41	260	<1	4	328	35	0.76	<5	9	<10	178	1342	<2	25	<10	4	33
95882	1185447	0.057	<1	3.17	12	405	<2	8	1.35	<4	7	12	28	1.57	0.46	11	0.57	542	<1	6	419	62	1.00	<5	6	<10	173	1669	<2	31	<10	4	99
95883	1185448	0.062	<1	2.64	14	399	<2	10	1.36	<4	7	11	33	1.62	0.45	10	0.53	539	<1	5	401	65	1.12	<5	8	<10	170	1603	<2	31	<10	4	156
95884	1185449	0.027	<1	3.99	11	434	<2	21	1.54	<4	8	16	21	1.78	0.37	10	0.71	511	<1	6	435	76	1.10	<5	6	<10	149	1616	4	32	<10	6	114
95885	1185450	0.249	<1	0.10	407	>5000	<2	8	0.85	<4	7	14	30	2.84	<0.01	3	0.21	<100	5	10	<100	22	0.88	18	10	<10	122	833	10	16	45	6	19
95886	1185451	0.019	<1	1.27	19	703	2	17	1.72	<4	9	16	63	1.91	<0.01	12	0.48	584	<1	6	393	31	1.19	<5	9	<10	166	1915	<2	37	<10	3	47
95887D	1185451	0.023	<1	1.06	15	602	2	12	1.76	<4	9	16	63	1.90	<0.01	11	0.48	597	<1	7	394	31	1.22	<5	8	<10	169	1926	<2	37	<10	3	48
95888	1185452	0.016	<1	1.20	9	562	2	21	2.28	<4	8	17	17	1.89	<0.01	13	0.75	811	<1	7	402	78	1.05	<5	13	<10	188	2047	3	38	<10	3	89
95889	1185453	0.028	<1	0.91	18	557	<2	7	1.22	<4	7	13	14	1.56	<0.01	12	0.50	607	<1	6	371	275	1.22	<5	7	<10	173	1895	<2	35	<10	3	473
95890	1185454	0.011	<1	1.35	20	549	2	9	0.82	<4	11	15	11	1.33	<0.01	12	0.47	478	<1	7	394	45	1.18	<5	11	<10	152	1900	<2	36	<10	3	215

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, May 22, 2012


Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/10/2012
 Date Completed: 04/24/2012
 Job #: 201241092
 Reference: TL 12 243
 Sample #: 209

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
95891	1185455	0.017	<1	1.20	29	507	2	1	0.76	<4	12	39	20	1.25	<0.01	10	0.50	510	<1	15	387	50	1.12	<5	8	<10	137	1946	<2	43	<10	3	260
95892	1185456	0.018	<1	3.03	29	478	2	6	0.94	<4	13	34	18	1.44	<0.01	15	0.77	514	<1	28	520	44	1.31	<5	8	<10	178	1831	3	39	<10	5	182
95893	1185457	0.022	<1	3.60	27	470	2	19	1.04	<4	10	25	9	1.31	<0.01	11	0.60	412	<1	21	382	47	1.29	<5	5	<10	124	1645	<2	34	<10	4	74
95894	1185458	0.043	<1	3.84	27	418	<2	14	2.04	<4	7	13	11	1.52	<0.01	13	1.06	822	<1	16	402	50	1.22	<5	9	<10	165	1637	6	31	<10	4	86
95895	1185459	0.008	<1	3.09	14	441	2	1	1.05	<4	4	11	4	0.69	<0.01	12	0.72	353	<1	12	325	31	0.65	<5	6	<10	146	1349	2	23	<10	3	23
95896	1185460	0.005	<1	3.91	6	370	<2	15	1.44	<4	12	26	19	2.19	0.25	6	0.84	423	<1	16	468	13	0.49	<5	7	<10	232	1884	5	73	24	12	35
95897	1185461	0.013	<1	1.41	10	743	2	11	1.26	<4	4	12	4	0.73	<0.01	7	0.46	291	<1	15	293	28	0.60	<5	7	<10	203	1255	<2	26	<10	2	22
95898D	1185461	0.007	<1	0.80	11	801	2	<1	1.32	<4	4	11	4	0.69	0.06	7	0.39	286	<1	11	275	25	0.61	<5	6	<10	214	1261	2	26	<10	2	19
95899	1185462	0.016	1	3.30	7	827	2	7	2.92	<4	18	46	29	2.95	<0.01	7	1.95	522	<1	75	1775	46	1.43	<5	6	<10	1143	2195	10	61	<10	13	68
95900	1185463	0.016	<1	3.29	10	692	2	9	2.79	<4	18	48	24	3.05	<0.01	13	2.06	501	<1	80	2003	42	1.36	<5	6	<10	667	2531	3	56	<10	13	76
95901	1185464	0.008	<1	1.00	7	775	2	8	1.04	<4	4	10	5	0.58	0.13	6	0.39	241	<1	10	318	22	0.47	<5	9	<10	234	1204	2	26	<10	2	18
95902	1185465	<0.005	<1	1.02	11	667	2	16	0.67	<4	5	7	1	0.54	0.12	12	0.38	247	<1	12	300	23	0.53	<5	<5	<10	165	1447	2	25	<10	2	17
95903	1185466	0.074	<1	1.79	23	607	2	18	0.66	<4	6	10	9	1.24	<0.01	14	0.63	405	<1	11	340	58	1.31	<5	9	<10	144	1398	<2	27	<10	3	240
95904	1185467	0.012	<1	3.04	10	809	3	4	2.37	<4	14	36	16	2.13	0.21	19	1.51	444	<1	52	1429	35	0.86	<5	8	<10	922	2087	3	50	<10	9	61
95905	1185468	0.076	<1	2.90	18	593	2	5	0.81	<4	5	10	10	1.16	0.08	11	0.55	319	<1	3	360	45	1.14	<5	12	<10	151	1291	2	25	<10	5	349
95906	1185469	<0.005	<1	2.70	15	551	<2	12	1.09	<4	4	8	4	0.90	0.28	7	0.41	276	<1	2	317	22	0.82	<5	7	<10	143	1160	<2	21	<10	3	42
95907	1185470	5.336	1	3.42	357	1416	2	12	2.15	<4	13	101	74	3.07	<0.01	11	1.07	427	7	39	723	29	1.27	35	7	<10	177	1610	11	113	<10	12	199
95908	1185471	0.040	<1	3.25	34	581	2	9	0.53	<4	6	9	9	1.34	0.35	11	0.37	191	<1	6	320	19	1.45	<5	10	<10	114	1194	<2	22	<10	4	50
95909D	1185471	0.039	<1	1.49	31	525	<2	12	0.44	<4	7	8	9	1.38	<0.01	11	0.30	202	<1	6	306	20	1.48	<5	7	<10	104	1251	2	22	<10	3	57
95910	1185472	0.016	<1	1.11	11	1012	2	5	0.82	<4	4	9	6	0.91	0.19	8	0.42	275	<1	5	273	36	0.72	<5	5	<10	190	1196	<2	24	<10	2	43

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By:  Jason Moore, General Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, May 22, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/10/2012
 Date Completed: 04/24/2012
 Job #: 201241092
 Reference: TL 12 243
 Sample #: 209

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
95911	1185473	0.011	1	3.51	8	1001	2	6	2.54	<4	17	44	27	2.80	<0.01	8	1.88	484	<1	66	1726	39	1.46	<5	5	<10	1164	2128	3	59	<10	13	67
95912	1185474	0.019	1	3.96	11	1181	2	23	2.87	<4	16	43	27	2.73	0.07	6	1.85	489	<1	64	1830	38	1.37	<5	7	<10	1362	2345	<2	59	<10	13	63
95913	1185475	0.018	<1	2.38	7	866	2	6	2.20	<4	13	33	14	2.13	0.25	11	1.33	410	<1	43	1202	31	0.75	<5	8	<10	691	2003	5	50	<10	7	59
95914	1185476	0.017	<1	2.52	7	675	<2	6	1.97	<4	12	33	15	2.14	0.05	12	1.41	404	<1	42	1230	26	0.77	<5	8	<10	549	1998	2	48	<10	9	58
95915	1185477	0.029	1	3.34	10	1290	2	13	3.19	<4	19	48	26	3.04	0.32	9	2.01	520	<1	75	1928	40	0.98	<5	5	<10	1638	2238	2	70	<10	14	101
95916	1185478	0.023	<1	2.57	11	633	2	6	3.18	<4	18	40	27	2.74	0.02	4	1.82	508	<1	63	1723	32	1.20	<5	5	<10	606	1805	2	65	<10	15	68
95917	1185479	0.064	<1	1.61	5	421	<2	15	0.83	<4	8	14	14	1.88	0.15	4	0.77	501	<1	9	391	15	0.78	<5	5	<10	124	1525	2	39	<10	5	57
95918	1185480	0.006	<1	1.71	7	376	<2	18	1.31	<4	12	28	20	2.28	<0.01	<1	0.75	440	<1	18	456	12	0.29	<5	10	<10	230	1915	<2	76	23	10	44
95919	1185481	0.123	<1	3.40	21	373	2	6	1.00	<4	10	24	15	1.89	<0.01	6	0.79	574	<1	14	367	30	1.26	<5	7	<10	134	1549	<2	37	<10	6	71
95920D	1185481	0.099	<1	3.16	19	435	2	23	1.21	<4	10	31	15	1.91	<0.01	9	0.75	601	<1	14	354	31	1.35	<5	6	<10	160	1636	<2	39	<10	5	71
95921	1185482	0.061	<1	2.86	24	208	<2	14	1.15	<4	9	30	22	1.82	<0.01	6	0.96	724	<1	13	481	74	1.52	<5	8	<10	110	1508	4	33	<10	7	189
95922	1185483	0.578	2	2.55	35	322	<2	<1	0.44	<4	6	21	29	1.53	<0.01	5	0.53	295	<1	7	413	287	1.61	<5	7	<10	99	1268	<2	25	<10	6	349
95923	1185484	0.328	4	2.88	57	285	<2	1	0.52	13	10	27	142	2.87	<0.01	6	0.79	555	<1	17	500	405	3.10	<5	10	<10	93	1590	2	34	49	7	4227
95924	1185485	0.022	1	3.59	12	383	<2	5	1.48	<4	8	46	16	1.91	<0.01	7	1.15	818	<1	18	605	46	1.00	5	10	<10	142	1663	2	36	<10	8	130
95925	1185486	0.023	1	2.99	20	335	<2	5	0.42	<4	7	13	18	1.29	0.37	7	0.71	631	<1	8	436	34	0.97	<5	6	<10	111	1465	5	29	<10	5	39
95926	1185487	0.189	2	2.51	24	305	<2	<1	0.23	<4	7	11	7	1.31	0.36	5	0.52	404	<1	7	368	82	1.24	<5	9	<10	99	1320	5	25	<10	5	102
95927	1185488	0.207	<1	2.77	12	394	<2	<1	0.92	<4	5	12	8	0.80	0.06	6	0.66	627	<1	5	328	58	0.54	<5	11	<10	166	1422	4	26	<10	3	69
95928	1185489	0.040	2	2.52	11	438	2	<1	1.11	<4	5	16	10	0.64	0.03	7	0.58	559	<1	5	297	75	0.49	<5	8	<10	196	1471	3	28	<10	3	177
95929	1185490	1.425	<1	3.08	17	413	2	17	1.29	<4	14	44	531	3.47	<0.01	5	0.97	548	20	30	585	71	0.88	<5	6	<10	197	1700	<2	100	20	12	94
95930	1185491	0.015	<1	2.88	13	330	2	<1	0.86	<4	5	14	13	0.70	<0.01	5	0.45	370	<1	4	309	21	0.58	<5	5	<10	161	1423	2	29	<10	3	18

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, May 22, 2012


Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/10/2012
 Date Completed: 04/24/2012
 Job #: 201241092
 Reference: TL 12 243
 Sample #: 209

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
95931D	1185491	0.015	<1	2.97	13	297	2	1	0.74	<4	6	15	11	0.70	0.12	6	0.48	370	<1	5	331	19	0.64	<5	9	<10	141	1441	<2	29	<10	3	16
95932	1185492	0.009	<1	1.46	11	201	<2	9	0.09	<4	4	13	4	0.79	<0.01	8	0.57	411	<1	4	383	37	0.83	<5	6	<10	39	1251	<2	22	<10	4	75
95933	1185493	0.007	<1	2.64	19	215	<2	11	1.02	<4	6	12	10	1.14	0.03	7	0.95	688	<1	6	352	33	0.62	<5	9	<10	92	1429	2	26	<10	4	146
95934	1185494	0.008	<1	3.60	7	208	<2	12	1.09	<4	5	19	4	1.13	<0.01	8	0.99	563	<1	4	332	21	0.52	<5	6	<10	105	1463	6	25	<10	4	37
95935	1185495	0.043	2	2.32	9	143	<2	3	0.71	<4	5	8	10	0.95	0.01	7	0.99	795	<1	4	364	380	0.48	<5	11	<10	72	1331	2	23	<10	4	144
95936	1185496	0.051	<1	3.62	10	196	<2	9	0.94	<4	5	9	30	1.00	<0.01	10	1.04	712	<1	3	347	64	0.59	<5	7	<10	91	1385	2	24	<10	4	314
95937	1185497	0.011	<1	2.41	10	134	<2	6	1.02	<4	5	9	4	1.26	0.04	7	1.14	864	<1	4	337	13	0.67	<5	8	<10	74	1281	5	22	<10	4	115
95938	1185498	0.011	<1	1.95	6	108	<2	14	0.91	<4	5	11	3	1.22	0.05	6	1.06	866	<1	6	326	13	0.57	<5	6	<10	69	1212	<2	21	<10	4	40
95939	1185499	0.008	<1	3.67	9	172	2	16	1.21	<4	6	12	5	1.69	0.16	12	1.03	792	<1	6	357	14	0.96	<5	8	<10	107	1442	7	25	<10	4	56
95940	1185500	0.007	<1	1.25	5	377	2	10	1.38	<4	12	28	20	2.28	<0.01	2	0.71	455	<1	20	442	9	0.34	<5	5	<10	235	2007	<2	78	26	9	38
95941	1185501	0.013	1	2.32	16	267	<2	23	1.28	<4	5	13	22	1.73	<0.01	9	0.65	751	<1	4	303	26	1.49	<5	5	<10	125	1339	<2	25	<10	3	138
95942R	1185501	0.014	1	2.43	16	205	<2	15	0.98	<4	5	14	22	1.68	0.07	8	0.68	735	<1	5	323	25	1.43	<5	<5	<10	96	1278	4	23	<10	3	113
95943	1185502	0.008	<1	2.70	17	210	<2	10	1.16	<4	5	9	6	1.11	0.06	8	0.65	582	<1	3	326	28	0.78	<5	7	<10	111	1414	2	24	<10	3	46
95944	1185503	0.012	<1	2.31	19	160	<2	14	0.94	<4	6	11	13	1.26	0.07	7	0.68	567	<1	5	326	41	1.06	<5	7	<10	90	1312	2	25	<10	3	105
95945	1185504	0.011	<1	1.80	24	175	<2	24	1.22	<4	5	25	5	1.21	0.03	8	0.55	521	<1	4	299	26	0.83	<5	9	<10	100	1380	<2	24	<10	3	53
95946	1185505	0.013	<1	1.84	26	48	<2	3	0.82	<4	5	23	5	1.47	<0.01	5	0.65	451	<1	6	364	16	1.22	<5	6	<10	61	1132	<2	19	<10	4	36
95947	1185506	<0.005	<1	2.51	25	134	<2	8	0.70	<4	5	24	7	1.21	<0.01	6	0.67	492	<1	4	361	16	0.87	<5	<5	<10	66	1293	<2	21	<10	4	278
95948	1185507	<0.005	<1	3.64	21	228	2	14	1.00	<4	4	20	6	1.16	<0.01	9	0.77	584	<1	5	389	26	0.85	<5	9	<10	101	1292	<2	23	<10	5	45
95949	1185508	<0.005	<1	2.43	15	203	<2	<1	0.88	<4	4	14	2	1.19	0.02	3	0.40	291	<1	4	370	10	0.97	<5	7	<10	89	1175	<2	20	<10	4	29
95950	1185509	<0.005	<1	1.78	7	324	<2	4	0.89	<4	4	11	3	1.25	0.14	4	0.38	295	<1	4	353	10	0.61	<5	10	<10	129	1163	<2	19	<10	5	28

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, May 22, 2012

Certificate of Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 04/10/2012
 Date Completed: 04/24/2012
 Job #: 201241092
 Reference: TL 12 243
 Sample #: 209

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
95951	1185510	0.267	<1	<0.01	319	>5000	2	7	0.64	<4	7	12	28	2.73	<0.01	<1	0.15	<100	4	10	<100	23	0.82	15	12	<10	128	309	9	13	31	5	16
95952	1185511	0.008	<1	2.70	15	463	2	7	0.78	<4	7	11	5	1.18	0.12	6	0.28	146	<1	8	316	18	1.36	<5	11	<10	193	1272	<2	25	<10	3	30
95953D	1185511	0.012	<1	2.33	12	301	2	3	0.90	<4	7	10	5	1.15	0.25	6	0.26	143	<1	7	295	17	1.37	<5	7	<10	213	1268	<2	25	<10	3	33
95954	1185512	0.022	1	2.66	13	379	2	5	1.12	<4	7	27	7	1.33	<0.01	8	0.51	285	<1	8	338	22	1.46	<5	10	<10	217	1301	<2	28	<10	3	45
95955	1185513	0.006	<1	3.26	20	411	2	6	1.31	<4	6	12	5	1.42	<0.01	6	0.63	339	<1	5	340	14	1.54	<5	6	<10	204	1226	<2	25	<10	4	40
95956	1185514	0.021	2	2.22	28	483	2	21	0.35	<4	7	29	16	1.29	<0.01	8	0.47	219	<1	9	383	15	1.38	<5	5	<10	111	1324	<2	31	<10	4	31
95957	1185515	0.020	2	2.33	35	429	2	13	0.61	<4	7	22	7	1.69	<0.01	7	0.66	405	<1	12	370	17	1.90	<5	9	<10	149	1088	<2	32	<10	4	33
95958	1185516	0.021	2	2.29	32	384	<2	1	0.21	<4	7	34	9	1.75	<0.01	9	0.75	402	<1	10	396	13	1.90	<5	7	<10	68	1030	2	30	<10	5	33
95959	1185517	0.012	2	2.90	37	532	<2	6	0.49	<4	11	68	21	2.18	<0.01	7	0.75	377	<1	29	459	18	2.14	<5	7	<10	113	1368	<2	48	<10	8	38
95960	1185518	0.013	1	2.88	28	452	2	5	0.42	<4	10	37	15	2.05	<0.01	7	0.75	335	<1	19	479	15	2.20	<5	6	<10	123	1321	2	38	<10	7	42
95961	1185519	0.022	1	3.01	29	344	<2	17	1.08	<4	16	75	40	3.18	<0.01	13	1.36	618	<1	39	439	18	2.92	5	11	<10	182	1517	<2	56	<10	10	56
95962	1185520	<0.005	<1	2.27	6	300	<2	14	1.27	<4	11	26	20	2.26	0.08	1	0.85	424	<1	20	477	13	0.36	<5	6	<10	193	1699	<2	73	19	12	37
95963	1185521	0.057	<1	2.43	11	496	2	18	1.27	<4	8	19	19	1.62	0.06	10	0.71	388	<1	7	443	64	0.97	<5	<5	<10	163	1824	<2	36	<10	4	120
95964D	1185521	0.036	<1	3.61	12	427	2	3	0.98	<4	8	16	20	1.68	0.09	11	0.86	395	<1	7	504	61	1.03	<5	7	<10	120	1768	<2	33	<10	5	122
95965	1185522	0.014	<1	3.66	7	392	2	<1	1.92	<4	8	8	7	1.87	0.08	9	1.00	407	<1	15	579	28	0.65	5	7	<10	131	1825	4	34	<10	6	62
95966	1185523	0.032	<1	4.50	17	550	2	5	2.37	<4	13	65	39	2.27	0.01	11	1.08	519	<1	35	550	45	0.92	<5	6	<10	180	2310	4	62	<10	8	73
95967	1185524	0.245	6	1.16	61	391	2	<1	0.18	<4	19	95	120	2.36	<0.01	7	0.37	224	<1	53	373	73	2.53	5	6	<10	63	1583	<2	67	<10	4	187
95968	1185525	0.631	20	1.03	74	236	2	13	<0.01	<4	9	24	49	1.67	<0.01	<1	0.23	<100	<1	24	305	477	2.14	12	6	<10	49	1104	<2	33	<10	3	448
95969	1185526	0.288	5	1.24	34	177	2	<1	0.01	<4	6	11	18	1.17	<0.01	1	0.25	126	<1	16	379	73	1.46	<5	7	<10	46	1026	2	27	<10	3	188
95970	1185527	0.109	3	2.08	41	148	<2	6	0.24	<4	6	12	15	1.45	<0.01	2	0.44	282	<1	14	428	61	1.62	<5	5	<10	58	895	<2	25	<10	3	165

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, May 22, 2012


Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/10/2012
 Date Completed: 04/24/2012
 Job #: 201241092
 Reference: TL 12 243
 Sample #: 209

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
95971	1185528	0.044	2	2.46	33	161	3	<1	<0.01	<4	6	12	7	0.94	<0.01	<1	0.22	<100	<1	15	387	42	1.12	<5	9	<10	43	862	<2	26	<10	5	35
95972	1185529	0.138	3	3.82	45	173	3	11	0.14	<4	6	9	13	1.47	<0.01	2	0.54	222	<1	13	475	60	1.59	<5	6	<10	57	836	<2	26	<10	5	92
95973	1185530	4.843	<1	1.54	338	1308	<2	15	1.76	<4	11	97	69	2.86	<0.01	4	1.01	385	5	43	691	23	1.06	20	7	<10	129	1281	7	103	<10	11	186
95974	1185531	0.057	2	3.36	48	221	3	3	<0.01	<4	6	9	10	1.23	<0.01	<1	0.33	<100	<1	14	452	51	1.41	<5	8	<10	50	909	<2	28	<10	4	65
95975D	1185531	0.080	3	1.60	35	252	3	6	<0.01	<4	7	10	10	1.22	<0.01	<1	0.25	<100	<1	15	377	74	1.43	5	9	<10	52	1186	<2	37	<10	2	77
95976	1185532	0.340	5	1.65	39	196	2	3	<0.01	<4	6	4	14	1.35	0.12	<1	0.19	<100	<1	16	408	57	1.66	<5	7	<10	44	901	<2	25	<10	3	149
95977	1185533	0.376	2	2.56	41	303	2	7	<0.01	<4	7	6	23	1.44	<0.01	<1	0.24	<100	<1	15	390	56	1.74	<5	6	<10	47	1020	<2	28	<10	3	96
95978	1185534	0.173	1	2.77	50	375	2	10	0.71	<4	7	12	26	1.43	<0.01	<1	0.57	421	<1	15	404	78	1.26	<5	5	<10	75	1193	<2	37	<10	3	100
95979	1185535	0.087	1	4.72	39	315	3	17	0.70	<4	7	17	24	1.33	<0.01	3	0.65	221	<1	19	368	73	1.25	<5	7	<10	68	1205	3	32	<10	5	106
95980	1185536	0.155	1	3.71	32	252	<2	11	0.72	<4	6	9	34	1.28	<0.01	<1	0.70	261	<1	17	418	70	1.09	<5	7	<10	59	997	<2	27	<10	5	127
95981	1185537	0.166	<1	1.98	39	323	3	10	0.60	<4	7	12	21	1.44	<0.01	11	0.42	356	<1	14	401	91	1.76	<5	5	<10	74	1366	2	36	11	3	384
95982	1185538	0.780	2	1.35	50	346	2	14	0.14	<4	8	42	25	1.52	<0.01	7	0.28	177	<1	7	405	107	1.72	6	7	<10	61	1429	<2	40	12	2	422
95983	1185539	0.514	2	1.54	39	305	2	16	0.47	<4	7	22	31	1.50	<0.01	7	0.46	474	<1	7	403	124	1.67	5	8	<10	71	1249	<2	35	<10	3	284
95984	1185540	0.015	<1	3.28	9	322	<2	7	2.26	<4	16	48	22	3.27	<0.01	13	1.19	668	<1	25	580	17	0.61	<5	9	<10	260	2750	<2	112	21	11	57
95985	1185541	0.992	3	1.32	62	304	2	7	<0.01	<4	6	16	42	1.63	<0.01	5	0.23	<100	<1	7	378	105	2.17	7	10	<10	57	1109	<2	31	12	2	541
95986D	1185541	1.064	3	2.08	70	291	2	11	<0.01	<4	7	16	41	1.63	<0.01	5	0.26	<100	<1	5	385	100	2.19	5	7	<10	57	1058	<2	29	10	3	544
95987	1185542	0.478	1	4.16	40	362	2	11	0.26	<4	7	12	48	1.49	<0.01	8	0.41	113	<1	6	460	82	1.93	<5	10	<10	71	1156	<2	31	<10	4	255
95988	1185543	0.365	2	4.08	27	477	2	<1	0.65	<4	7	23	45	1.27	<0.01	24	0.52	232	<1	10	419	70	1.88	<5	8	<10	90	1602	4	36	<10	4	118
95989	1185544	0.667	2	3.17	35	450	2	<1	0.48	<4	8	35	23	1.54	<0.01	15	0.40	274	<1	5	407	63	1.87	<5	5	<10	74	1502	2	33	<10	3	207
95990	1185545	0.873	2	2.38	32	243	2	8	0.10	<4	6	13	30	1.16	0.07	<1	0.33	130	<1	6	429	56	1.28	<5	10	<10	44	864	<2	20	<10	5	130

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, May 22, 2012


Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/10/2012
 Date Completed: 04/24/2012
 Job #: 201241092
 Reference: TL 12 243
 Sample #: 209

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
95991	1185546	0.332	<1	0.71	39	178	2	2	0.19	<4	7	16	21	1.30	0.18	<1	0.37	184	<1	8	453	56	1.27	<5	5	<10	43	687	<2	15	<10	4	122
95992	1185547	0.077	<1	3.26	66	273	<2	6	1.04	<4	8	22	31	1.53	0.52	3	0.82	471	<1	8	540	69	1.18	<5	6	<10	66	1105	<2	22	<10	6	128
95993	1185548	1.771	20	2.54	69	482	2	14	1.33	13	8	25	175	2.69	<0.01	16	0.68	576	<1	7	451	1384	2.98	19	6	<10	86	1951	<2	36	39	4	2595
95994	1185549	0.015	<1	2.17	26	498	2	10	2.07	<4	9	23	5	1.84	<0.01	16	0.81	634	<1	8	452	62	1.06	<5	<5	<10	106	2218	<2	40	<10	3	93
95995	1185550	1.442	1	2.00	20	501	2	15	1.43	4	15	51	555	3.58	<0.01	11	0.79	584	21	31	588	75	1.08	<5	5	<10	231	2041	<2	108	27	8	98
95996	1185551	0.042	<1	2.50	15	477	2	9	2.07	<4	8	29	16	1.78	<0.01	18	0.82	504	<1	10	437	50	0.88	<5	7	<10	122	2087	2	39	<10	3	80
95997D	1185551	0.069	<1	4.06	19	473	2	3	2.19	<4	8	28	10	1.82	<0.01	16	1.00	508	<1	8	459	50	0.77	<5	10	<10	121	2053	7	38	<10	4	83
95998	1185552	1.500	5	2.42	113	242	2	26	0.41	8	15	81	202	3.62	<0.01	8	0.39	185	9	33	328	468	4.21	5	6	<10	66	1643	<2	43	21	5	1609
95999	1185553	0.256	2	4.91	52	341	3	20	1.07	5	21	148	64	3.86	<0.01	19	1.03	568	<1	55	542	138	2.82	<5	<5	<10	90	2474	5	91	10	11	602
96000	1185554	0.307	1	4.02	47	408	3	7	0.59	<4	16	105	41	2.50	<0.01	32	0.62	319	<1	30	438	57	2.79	<5	8	<10	84	2385	2	73	10	6	227
96001	1185555	0.574	1	3.94	53	402	3	13	0.66	<4	8	41	24	2.01	0.03	19	0.51	262	<1	12	413	84	2.51	<5	8	<10	84	1735	<2	41	<10	4	165
96002	1185556	0.419	<1	1.87	42	172	2	13	0.63	<4	8	42	29	1.90	0.12	<1	0.65	336	<1	15	476	83	1.70	<5	7	<10	56	937	<2	25	<10	6	139
96003	1185557	0.197	<1	1.26	57	154	2	17	0.29	<4	5	29	43	1.68	0.22	<1	0.47	206	<1	9	436	188	1.64	<5	9	<10	57	819	<2	18	<10	6	430
96004	1185558	0.179	<1	1.04	52	150	<2	11	0.11	<4	5	24	26	1.49	0.24	<1	0.37	168	<1	6	405	87	1.51	<5	5	<10	45	818	<2	17	<10	5	193
96005	1185559	0.064	<1	3.18	20	439	2	25	1.98	<4	8	35	5	1.73	<0.01	15	0.90	543	<1	7	482	37	1.13	<5	8	<10	134	2072	<2	40	<10	4	69
96006	1185560	<0.005	1	3.77	8	382	<2	12	2.49	<4	16	52	23	3.50	<0.01	14	1.25	712	<1	26	606	13	0.58	<5	10	<10	295	3049	<2	121	21	12	53
96007	1185561	0.062	<1	2.54	22	405	2	21	1.91	<4	7	25	10	1.60	<0.01	16	0.80	558	<1	6	454	50	1.07	5	7	<10	122	2105	<2	40	<10	4	71
96008R	1185561	0.050	<1	2.63	25	421	2	<1	2.04	<4	8	41	11	1.74	<0.01	17	0.79	590	<1	7	465	53	1.12	<5	8	<10	128	2154	2	41	<10	4	72
96009	1185562	0.106	<1	2.73	39	344	2	14	1.22	<4	8	18	27	1.53	<0.01	14	0.69	446	<1	7	433	61	1.41	<5	9	<10	93	1851	<2	36	10	4	387
96010	1185563	0.395	6	3.28	18	451	2	6	1.24	<4	7	34	31	1.62	<0.01	17	0.61	334	<1	10	455	802	1.21	5	5	<10	113	2002	2	37	<10	4	232

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By:  Jason Moore, General Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, May 22, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/10/2012
 Date Completed: 04/24/2012
 Job #: 201241092
 Reference: TL 12 243
 Sample #: 209

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
96011	1185564	0.021	<1	4.92	8	347	2	8	1.99	<4	8	26	17	1.79	<0.01	18	0.89	396	<1	8	502	35	0.74	<5	10	<10	171	2052	<2	37	<10	5	58
96012	1185565	0.009	<1	4.40	7	303	<2	2	1.85	<4	7	18	7	1.66	<0.01	20	0.88	314	<1	8	489	24	0.82	<5	<5	<10	161	1843	4	34	<10	5	45
96013	1185566	0.257	2	3.87	12	291	2	16	1.87	4	7	37	76	1.82	<0.01	21	0.77	374	<1	7	430	202	1.15	<5	12	<10	144	1909	2	34	11	4	746
96014	1185567	0.020	<1	3.04	8	133	<2	22	1.61	<4	5	27	14	1.37	<0.01	8	1.17	393	<1	5	402	30	0.43	<5	5	<10	81	1051	5	20	<10	5	67
96015	1185568	0.073	<1	1.65	16	86	2	10	0.27	<4	3	31	20	1.07	0.13	7	0.81	259	<1	4	217	23	0.69	<5	8	<10	57	628	<2	9	<10	4	63
96016	1185569	0.100	<1	1.30	18	63	<2	2	0.29	<4	3	21	34	1.06	0.20	5	0.85	259	<1	3	213	31	0.68	<5	8	<10	47	634	<2	9	<10	4	295
96017	1185570	0.221	<1	1.57	406	>5000	2	11	0.95	<4	8	14	30	2.81	<0.01	6	0.27	<100	5	12	<100	24	0.99	20	7	<10	127	850	5	15	47	8	24
96018	1185571	0.287	<1	2.86	28	337	2	3	0.25	9	4	29	30	1.14	<0.01	17	0.47	164	<1	3	191	66	1.39	<5	7	<10	78	1101	2	18	32	3	2443
96019D	1185571	0.306	<1	2.93	24	250	2	8	0.25	9	4	31	30	1.13	<0.01	17	0.47	163	<1	3	185	66	1.41	<5	7	<10	78	1071	<2	17	29	3	2420
96020	1185572	0.183	<1	3.09	20	306	2	<1	0.75	<4	4	44	18	1.23	<0.01	20	0.60	272	<1	3	211	37	1.18	<5	9	<10	94	1180	<2	19	<10	3	133
96021	1185573	0.025	<1	4.89	9	292	2	15	2.57	<4	5	32	6	1.47	<0.01	15	1.62	510	<1	9	290	22	0.85	<5	7	<10	146	1130	9	21	<10	5	431
96022	1185574	0.030	<1	3.09	6	267	2	16	1.74	<4	4	10	11	1.07	<0.01	17	0.94	359	<1	19	214	20	0.75	<5	10	<10	118	1079	<2	17	<10	3	67
96023	1185575	0.033	<1	4.35	10	219	2	25	1.66	<4	4	8	7	1.13	<0.01	18	1.03	319	<1	13	223	21	0.90	<5	8	<10	108	994	7	17	<10	4	43
96024	1185576	0.020	<1	4.35	10	253	2	8	1.78	<4	3	7	5	1.08	<0.01	24	0.97	323	<1	10	227	26	1.06	<5	8	<10	121	1095	<2	17	<10	4	30
96025	1185577	0.029	1	4.69	11	307	2	23	1.91	<4	4	6	14	1.09	<0.01	23	1.08	389	<1	8	230	41	1.06	<5	12	<10	126	1135	4	17	<10	4	203
96026	1185578	0.080	<1	1.36	16	40	2	12	2.54	8	3	9	263	2.50	<0.01	<1	1.39	496	<1	17	169	48	1.82	<5	5	<10	95	600	4	10	26	3	2186
96027	1185579	0.059	10	1.71	6	18	2	19	3.54	39	4	20	188	2.85	<0.01	4	2.01	767	<1	35	191	1266	2.22	<5	11	<10	70	616	7	13	131	4	12151
96028	1185580	<0.005	<1	0.87	7	155	2	<1	1.67	<4	14	43	24	3.15	<0.01	3	1.31	602	<1	28	577	18	0.26	<5	9	<10	134	2144	6	99	14	13	126
96029	1185581	0.056	<1	4.92	10	277	2	8	2.71	<4	3	10	12	1.41	<0.01	16	1.76	523	<1	15	218	176	0.96	<5	11	<10	151	904	11	17	<10	5	394
96030D	1185581	0.062	<1	4.58	9	279	2	10	2.61	<4	3	9	11	1.33	<0.01	15	1.68	502	<1	12	203	170	0.92	<5	11	<10	149	885	11	15	<10	5	381

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, May 22, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/10/2012
 Date Completed: 04/24/2012
 Job #: 201241092
 Reference: TL 12 243
 Sample #: 209

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
96031	1185582	0.015	<1	6.75	8	497	<2	26	3.26	5	3	6	6	1.36	<0.01	24	2.86	850	<1	13	210	31	0.64	<5	12	<10	238	1015	8	16	12	7	701
96032	1185583	0.011	<1	4.64	5	437	2	6	0.89	<4	4	7	10	1.08	<0.01	24	1.46	308	<1	14	227	33	0.84	<5	<5	<10	135	1154	<2	18	<10	4	111
96033	1185584	0.047	<1	4.84	4	384	2	18	1.08	<4	4	7	19	1.19	<0.01	24	1.79	379	<1	15	233	39	0.80	<5	11	<10	127	1028	4	16	<10	4	103
96034	1185585	0.112	<1	3.74	4	316	2	4	0.73	8	4	7	91	1.35	<0.01	20	1.56	340	<1	14	219	41	1.07	<5	8	<10	108	1020	<2	17	19	4	1637
96035	1185586	0.063	<1	3.99	10	364	<2	5	0.55	<4	4	7	18	1.28	<0.01	19	1.34	277	<1	10	211	58	1.02	<5	7	<10	98	1032	3	17	<10	4	233
96036	1185587	0.018	<1	4.03	9	339	2	30	1.11	<4	4	6	1	1.08	<0.01	26	1.25	383	<1	11	212	15	1.03	<5	6	<10	133	1099	5	17	<10	4	45
96037	1185588	0.018	<1	3.82	7	459	2	11	0.99	<4	4	6	2	0.99	<0.01	22	0.80	232	<1	11	222	13	0.88	<5	6	<10	130	1168	<2	18	<10	3	31
96038	1185589	0.025	<1	1.68	10	221	<2	23	0.99	6	4	17	37	1.32	<0.01	10	1.47	389	<1	25	249	29	0.76	<5	8	<10	86	840	<2	16	11	4	1031
96039	1185590	5.127	1	0.51	354	1257	2	10	1.76	4	12	100	75	2.99	<0.01	2	1.04	397	6	46	718	26	1.04	13	7	<10	107	1277	4	104	<10	11	213

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By:  Jason Moore, General Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, April 24, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/10/2012
 Date Completed: 04/24/2012
 Job #: 201241092
 Reference: TL 12 243
 Sample #: 209

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
95811	1185382	35	0.001	0.035
95812	1185383	40	0.001	0.040
95813	1185384	86	0.002	0.086
95814	1185385	347	0.010	0.347
95815	1185386	61	0.002	0.061
95816	1185387	135	0.004	0.135
95817	1185388	183	0.005	0.183
95818	1185389	484	0.014	0.484
95819	1185390	254	0.007	0.254
95820	1185391	1989	0.058	1.989
95821 Dup	1185391	2028	0.059	2.028
95822	1185392	4536	0.132	4.536
95823	1185393	217	0.006	0.217
95824	1185394	76	0.002	0.076
95825	1185395	111	0.003	0.111
95826	1185396	106	0.003	0.106
95827	1185397	212	0.006	0.212
95828	1185398	22	<0.001	0.022
95829	1185399	19	<0.001	0.019
95830	1185400	<5	<0.001	<0.005
95831	1185401	24	<0.001	0.024
95832 Dup	1185401	20	<0.001	0.020
95833	1185402	33	<0.001	0.033
95834	1185403	146	0.004	0.146
95835	1185404	35	0.001	0.035
95836	1185405	805	0.023	0.805
95837	1185406	67	0.002	0.067
95838	1185407	20	<0.001	0.020
95839	1185408	40	0.001	0.040
95840	1185409	48	0.001	0.048

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, April 24, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/10/2012
 Date Completed: 04/24/2012
 Job #: 201241092
 Reference: TL 12 243
 Sample #: 209

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
95841	1185410	4966	0.145	4.966
95842	1185411	31	<0.001	0.031
95843 Dup	1185411	28	<0.001	0.028
95844	1185412	41	0.001	0.041
95845	1185413	15	<0.001	0.015
95846	1185414	19	<0.001	0.019
95847	1185415	15	<0.001	0.015
95848	1185416	<5	<0.001	<0.005
95849	1185417	16	<0.001	0.016
95850	1185418	55	0.002	0.055
95851	1185419	35	0.001	0.035
95852	1185420	<5	<0.001	<0.005
95853	1185421	48	0.001	0.048
95854 Dup	1185421	63	0.002	0.063
95855	1185422	28	<0.001	0.028
95856	1185423	30	<0.001	0.030
95857	1185424	15	<0.001	0.015
95858	1185425	<5	<0.001	<0.005
95859	1185426	5	<0.001	0.005
95860	1185427	<5	<0.001	<0.005
95861	1185428	<5	<0.001	<0.005
95862	1185429	10	<0.001	0.010
95863	1185430	1490	0.043	1.490
95864	1185431	<5	<0.001	<0.005
95865 Dup	1185431	22	<0.001	0.022
95866	1185432	19	<0.001	0.019
95867	1185433	16	<0.001	0.016
95868	1185434	39	0.001	0.039
95869	1185435	17	<0.001	0.017
95870	1185436	6	<0.001	0.006

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, April 24, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/10/2012
 Date Completed: 04/24/2012
 Job #: 201241092
 Reference: TL 12 243
 Sample #: 209

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
95871	1185437	6	<0.001	0.006
95872	1185438	19	<0.001	0.019
95873	1185439	14	<0.001	0.014
95874	1185440	<5	<0.001	<0.005
95875	1185441	<5	<0.001	<0.005
95876 Rep	1185441	9	<0.001	0.009
95877	1185442	<5	<0.001	<0.005
95878	1185443	31	<0.001	0.031
95879	1185444	<5	<0.001	<0.005
95880	1185445	16	<0.001	0.016
95881	1185446	14	<0.001	0.014
95882	1185447	57	0.002	0.057
95883	1185448	62	0.002	0.062
95884	1185449	27	<0.001	0.027
95885	1185450	249	0.007	0.249
95886	1185451	19	<0.001	0.019
95887 Dup	1185451	23	<0.001	0.023
95888	1185452	16	<0.001	0.016
95889	1185453	28	<0.001	0.028
95890	1185454	11	<0.001	0.011
95891	1185455	17	<0.001	0.017
95892	1185456	18	<0.001	0.018
95893	1185457	22	<0.001	0.022
95894	1185458	43	0.001	0.043
95895	1185459	8	<0.001	0.008
95896	1185460	5	<0.001	0.005
95897	1185461	13	<0.001	0.013
95898 Dup	1185461	7	<0.001	0.007
95899	1185462	16	<0.001	0.016
95900	1185463	16	<0.001	0.016

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, April 24, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/10/2012
 Date Completed: 04/24/2012
 Job #: 201241092
 Reference: TL 12 243
 Sample #: 209

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
95901	1185464	8	<0.001	0.008
95902	1185465	<5	<0.001	<0.005
95903	1185466	74	0.002	0.074
95904	1185467	12	<0.001	0.012
95905	1185468	76	0.002	0.076
95906	1185469	<5	<0.001	<0.005
95907	1185470	5336	0.156	5.336
95908	1185471	40	0.001	0.040
95909 Dup	1185471	39	0.001	0.039
95910	1185472	16	<0.001	0.016
95911	1185473	11	<0.001	0.011
95912	1185474	19	<0.001	0.019
95913	1185475	18	<0.001	0.018
95914	1185476	17	<0.001	0.017
95915	1185477	29	<0.001	0.029
95916	1185478	23	<0.001	0.023
95917	1185479	64	0.002	0.064
95918	1185480	6	<0.001	0.006
95919	1185481	123	0.004	0.123
95920 Dup	1185481	99	0.003	0.099
95921	1185482	61	0.002	0.061
95922	1185483	578	0.017	0.578
95923	1185484	328	0.010	0.328
95924	1185485	22	<0.001	0.022
95925	1185486	23	<0.001	0.023
95926	1185487	189	0.006	0.189
95927	1185488	207	0.006	0.207
95928	1185489	40	0.001	0.040
95929	1185490	1425	0.042	1.425
95930	1185491	15	<0.001	0.015

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, April 24, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/10/2012
 Date Completed: 04/24/2012
 Job #: 201241092
 Reference: TL 12 243
 Sample #: 209

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
95931 Dup	1185491	15	<0.001	0.015
95932	1185492	9	<0.001	0.009
95933	1185493	7	<0.001	0.007
95934	1185494	8	<0.001	0.008
95935	1185495	43	0.001	0.043
95936	1185496	51	0.001	0.051
95937	1185497	11	<0.001	0.011
95938	1185498	11	<0.001	0.011
95939	1185499	8	<0.001	0.008
95940	1185500	7	<0.001	0.007
95941	1185501	13	<0.001	0.013
95942 Rep	1185501	14	<0.001	0.014
95943	1185502	8	<0.001	0.008
95944	1185503	12	<0.001	0.012
95945	1185504	11	<0.001	0.011
95946	1185505	13	<0.001	0.013
95947	1185506	<5	<0.001	<0.005
95948	1185507	<5	<0.001	<0.005
95949	1185508	<5	<0.001	<0.005
95950	1185509	<5	<0.001	<0.005
95951	1185510	267	0.008	0.267
95952	1185511	8	<0.001	0.008
95953 Dup	1185511	12	<0.001	0.012
95954	1185512	22	<0.001	0.022
95955	1185513	6	<0.001	0.006
95956	1185514	21	<0.001	0.021
95957	1185515	20	<0.001	0.020
95958	1185516	21	<0.001	0.021
95959	1185517	12	<0.001	0.012
95960	1185518	13	<0.001	0.013

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, April 24, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/10/2012
 Date Completed: 04/24/2012
 Job #: 201241092
 Reference: TL 12 243
 Sample #: 209

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
95961	1185519	22	<0.001	0.022
95962	1185520	<5	<0.001	<0.005
95963	1185521	57	0.002	0.057
95964 Dup	1185521	36	0.001	0.036
95965	1185522	14	<0.001	0.014
95966	1185523	32	<0.001	0.032
95967	1185524	245	0.007	0.245
95968	1185525	631	0.018	0.631
95969	1185526	288	0.008	0.288
95970	1185527	109	0.003	0.109
95971	1185528	44	0.001	0.044
95972	1185529	138	0.004	0.138
95973	1185530	4843	0.141	4.843
95974	1185531	57	0.002	0.057
95975 Dup	1185531	80	0.002	0.080
95976	1185532	340	0.010	0.340
95977	1185533	376	0.011	0.376
95978	1185534	173	0.005	0.173
95979	1185535	87	0.003	0.087
95980	1185536	155	0.005	0.155
95981	1185537	166	0.005	0.166
95982	1185538	780	0.023	0.780
95983	1185539	514	0.015	0.514
95984	1185540	15	<0.001	0.015
95985	1185541	992	0.029	0.992
95986 Dup	1185541	1064	0.031	1.064
95987	1185542	478	0.014	0.478
95988	1185543	365	0.011	0.365
95989	1185544	667	0.019	0.667
95990	1185545	873	0.025	0.873

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, April 24, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/10/2012
 Date Completed: 04/24/2012
 Job #: 201241092
 Reference: TL 12 243
 Sample #: 209

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
95991	1185546	332	0.010	0.332
95992	1185547	77	0.002	0.077
95993	1185548	1771	0.052	1.771
95994	1185549	15	<0.001	0.015
95995	1185550	1442	0.042	1.442
95996	1185551	42	0.001	0.042
95997 Dup	1185551	69	0.002	0.069
95998	1185552	1500	0.044	1.500
95999	1185553	256	0.007	0.256
96000	1185554	307	0.009	0.307
96001	1185555	574	0.017	0.574
96002	1185556	419	0.012	0.419
96003	1185557	197	0.006	0.197
96004	1185558	179	0.005	0.179
96005	1185559	64	0.002	0.064
96006	1185560	<5	<0.001	<0.005
96007	1185561	62	0.002	0.062
96008 Rep	1185561	50	0.001	0.050
96009	1185562	106	0.003	0.106
96010	1185563	395	0.012	0.395
96011	1185564	21	<0.001	0.021
96012	1185565	9	<0.001	0.009
96013	1185566	257	0.008	0.257
96014	1185567	20	<0.001	0.020
96015	1185568	73	0.002	0.073
96016	1185569	100	0.003	0.100
96017	1185570	221	0.006	0.221
96018	1185571	287	0.008	0.287
96019 Dup	1185571	306	0.009	0.306
96020	1185572	183	0.005	0.183

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, April 24, 2012

Certificate of Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 04/10/2012
 Date Completed: 04/24/2012
 Job #: 201241092
 Reference: TL 12 243
 Sample #: 209

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
96021	1185573	25	<0.001	0.025
96022	1185574	30	<0.001	0.030
96023	1185575	33	<0.001	0.033
96024	1185576	20	<0.001	0.020
96025	1185577	29	<0.001	0.029
96026	1185578	80	0.002	0.080
96027	1185579	59	0.002	0.059
96028	1185580	<5	<0.001	<0.005
96029	1185581	56	0.002	0.056
96030 Dup	1185581	62	0.002	0.062
96031	1185582	15	<0.001	0.015
96032	1185583	11	<0.001	0.011
96033	1185584	47	0.001	0.047
96034	1185585	112	0.003	0.112
96035	1185586	63	0.002	0.063
96036	1185587	18	<0.001	0.018
96037	1185588	18	<0.001	0.018
96038	1185589	25	<0.001	0.025
96039	1185590	5127	0.150	5.127

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AlSu1

 Certified By: 
 Derek Demianliuk H. Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Thursday, April 26, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/17/2012
 Date Completed: 04/26/2012
 Job #: 201241199
 Reference: TL 12 244
 Sample #: 332

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
103338	1185590	No Sample Received		
103339	1185591	<5	<0.001	<0.005
103340	1185592	6	<0.001	0.006
103341	1185593	19	<0.001	0.019
103342	1185594	13	<0.001	0.013
103343	1185595	25	<0.001	0.025
103344	1185596	7	<0.001	0.007
103345	1185597	5	<0.001	0.005
103346	1185598	<5	<0.001	<0.005
103347	1185599	<5	<0.001	<0.005
103348 Dup	1185599	<5	<0.001	<0.005
103349	1185600	<5	<0.001	<0.005
103350	1185601	6	<0.001	0.006
103351	1185602	<5	<0.001	<0.005
103352	1185603	<5	<0.001	<0.005
103353	1185604	13	<0.001	0.013
103354	1185605	8	<0.001	0.008
103355	1185606	9	<0.001	0.009
103356	1185607	25	<0.001	0.025
103357	1185608	11	<0.001	0.011
103358	1185609	19	<0.001	0.019
103359 Dup	1185609	12	<0.001	0.012
103360	1185610	1309	0.038	1.309
103361	1185611	5	<0.001	0.005
103362	1185612	<5	<0.001	<0.005
103363	1185613	<5	<0.001	<0.005
103364	1185614	13	<0.001	0.013
103365	1185615	45	0.001	0.045
103366	1185616	22	<0.001	0.022
103367	1185617	6	<0.001	0.006

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Thursday, April 26, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/17/2012
 Date Completed: 04/26/2012
 Job #: 201241199
 Reference: TL 12 244
 Sample #: 332

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
103368	1185618	16	<0.001	0.016
103369	1185619	25	<0.001	0.025
103370 Dup	1185619	40	0.001	0.040
103371	1185620	8	<0.001	0.008
103372	1185621	17	<0.001	0.017
103373	1185622	17	<0.001	0.017
103374	1185623	18	<0.001	0.018
103375	1185624	16	<0.001	0.016
103376	1185625	18	<0.001	0.018
103377	1185626	19	<0.001	0.019
103378	1185627	20	<0.001	0.020
103379	1185628	18	<0.001	0.018
103380	1185629	20	<0.001	0.020
103381 Dup	1185629	20	<0.001	0.020
103382	1185630	258	0.008	0.258
103383	1185631	52	0.002	0.052
103384	1185632	87	0.003	0.087
103385	1185633	24	<0.001	0.024
103386	1185634	69	0.002	0.069
103387	1185635	51	0.001	0.051
103388	1185636	25	<0.001	0.025
103389	1185637	<5	<0.001	<0.005
103390	1185638	10	<0.001	0.010
103391	1185639	38	0.001	0.038
103392 Dup	1185639	28	<0.001	0.028
103393	1185640	<5	<0.001	<0.005
103394	1185641	19	<0.001	0.019
103395	1185642	85	0.002	0.085
103396	1185643	15	<0.001	0.015
103397	1185644	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Thursday, April 26, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/17/2012
 Date Completed: 04/26/2012
 Job #: 201241199
 Reference: TL 12 244
 Sample #: 332

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
103398	1185645	26	<0.001	0.026
103399	1185646	<5	<0.001	<0.005
103400	1185647	9	<0.001	0.009
103401	1185648	36	0.001	0.036
103402	1185649	<5	<0.001	<0.005
103403 Rep	1185649	<5	<0.001	<0.005
103404	1185650	4841	0.141	4.841
103405	1185651	<5	<0.001	<0.005
103406	1185652	16	<0.001	0.016
103407	1185653	<5	<0.001	<0.005
103408	1185654	<5	<0.001	<0.005
103409	1185655	<5	<0.001	<0.005
103410	1185656	<5	<0.001	<0.005
103411	1185657	11	<0.001	0.011
103412	1185658	80	0.002	0.080
103413	1185659	14	<0.001	0.014
103414 Dup	1185659	14	<0.001	0.014
103415	1185660	<5	<0.001	<0.005
103416	1185661	12	<0.001	0.012
103417	1185662	15	<0.001	0.015
103418	1185663	6	<0.001	0.006
103419	1185664	5	<0.001	0.005
103420	1185665	12	<0.001	0.012
103421	1185666	<5	<0.001	<0.005
103422	1185667	<5	<0.001	<0.005
103423	1185668	10	<0.001	0.010
103424	1185669	8	<0.001	0.008
103425 Dup	1185669	10	<0.001	0.010
103426	1185670	1101	0.032	1.101
103427	1185671	7	<0.001	0.007

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Thursday, April 26, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/17/2012
 Date Completed: 04/26/2012
 Job #: 201241199
 Reference: TL 12 244
 Sample #: 332

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
103428	1185672	<5	<0.001	<0.005
103429	1185673	<5	<0.001	<0.005
103430	1185674	9	<0.001	0.009
103431	1185675	93	0.003	0.093
103432	1185676	117	0.003	0.117
103433	1185677	18	<0.001	0.018
103434	1185678	5	<0.001	0.005
103435	1185679	38	0.001	0.038
103436 Dup	1185679	12	<0.001	0.012
103437	1185680	<5	<0.001	<0.005
103438	1185681	<5	<0.001	<0.005
103439	1185682	9	<0.001	0.009
103440	1185683	26	<0.001	0.026
103441	1185684	34	<0.001	0.034
103442	1185685	80	0.002	0.080
103443	1185686	41	0.001	0.041
103444	1185687	8	<0.001	0.008
103445	1185688	17	<0.001	0.017
103446	1185689	10	<0.001	0.010
103447 Dup	1185689	6	<0.001	0.006
103448	1185690	233	0.007	0.233
103449	1185691	79	0.002	0.079
103450	1185692	48	0.001	0.048
103451	1185693	14	<0.001	0.014
103452	1185694	71	0.002	0.071
103453	1185695	<5	<0.001	<0.005
103454	1185696	7	<0.001	0.007
103455	1185697	7	<0.001	0.007
103456	1185698	101	0.003	0.101
103457	1185699	68	0.002	0.068

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Thursday, April 26, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/17/2012
 Date Completed: 04/26/2012
 Job #: 201241199
 Reference: TL 12 244
 Sample #: 332

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
103458 Dup	1185699	89	0.003	0.089
103459	1185700	<5	<0.001	<0.005
103460	1185701	16	<0.001	0.016
103461	1185702	118	0.003	0.118
103462	1185703	14	<0.001	0.014
103463	1185704	11	<0.001	0.011
103464	1185705	8	<0.001	0.008
103465	1185706	<5	<0.001	<0.005
103466	1185707	<5	<0.001	<0.005
103467	1185708	<5	<0.001	<0.005
103468	1185709	9	<0.001	0.009
103469 Rep	1185709	14	<0.001	0.014
103470	1185710	4977	0.145	4.977
103471	1185711	247	0.007	0.247
103472	1185712	151	0.004	0.151
103473	1185713	53	0.002	0.053
103474	1185714	<5	<0.001	<0.005
103475	1185715	<5	<0.001	<0.005
103476	1185716	<5	<0.001	<0.005
103477	1185717	<5	<0.001	<0.005
103478	1185718	<5	<0.001	<0.005
103479	1185719	<5	<0.001	<0.005
103480 Dup	1185719	<5	<0.001	<0.005
103481	1185720	<5	<0.001	<0.005
103482	1185721	12	<0.001	0.012
103483	1185722	30	<0.001	0.030
103484	1185723	144	0.004	0.144
103485	1185724	87	0.003	0.087
103486	1185725	235	0.007	0.235
103487	1185726	132	0.004	0.132

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Thursday, April 26, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/17/2012
 Date Completed: 04/26/2012
 Job #: 201241199
 Reference: TL 12 244
 Sample #: 332

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
103488	1185727	96	0.003	0.096
103489	1185728	18	<0.001	0.018
103490	1185729	<5	<0.001	<0.005
103491 Dup	1185729	<5	<0.001	<0.005
103492	1185730	1195	0.035	1.195
103493	1185731	31	<0.001	0.031
103494	1185732	82	0.002	0.082
103495	1185733	59	0.002	0.059
103496	1185734	32	<0.001	0.032
103497	1185735	47	0.001	0.047
103498	1185736	47	0.001	0.047
103499	1185737	48	0.001	0.048
103500	1185738	41	0.001	0.041
103501	1185739	94	0.003	0.094
103502 Dup	1185739	101	0.003	0.101
103503	1185740	<5	<0.001	<0.005
103504	1185741	196	0.006	0.196
103505	1185742	408	0.012	0.408
103506	1185743	240	0.007	0.240
103507	1185744	313	0.009	0.313
103508	1185745	189	0.006	0.189
103509	1185746	181	0.005	0.181
103510	1185747	275	0.008	0.275
103511	1185748	232	0.007	0.232
103512	1185749	289	0.008	0.289
103513 Dup	1185749	268	0.008	0.268
103514	1185750	235	0.007	0.235
103515	1185751	68	0.002	0.068
103516	1185752	29	<0.001	0.029
103517	1185753	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Thursday, April 26, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/17/2012
 Date Completed: 04/26/2012
 Job #: 201241199
 Reference: TL 12 244
 Sample #: 332

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
103518	1185754	<5	<0.001	<0.005
103519	1185755	5	<0.001	0.005
103520	1185756	<5	<0.001	<0.005
103521	1185757	<5	<0.001	<0.005
103522	1185758	11	<0.001	0.011
103523	1185759	11	<0.001	0.011
103524 Dup	1185759	<5	<0.001	<0.005
103525	1185760	<5	<0.001	<0.005
103526	1185761	<5	<0.001	<0.005
103527	1185762	<5	<0.001	<0.005
103528	1185763	<5	<0.001	<0.005
103529	1185764	<5	<0.001	<0.005
103530	1185765	<5	<0.001	<0.005
103531	1185766	<5	<0.001	<0.005
103532	1185767	<5	<0.001	<0.005
103533	1185768	17	<0.001	0.017
103534	1185769	44	0.001	0.044
103535 Rep	1185769	58	0.002	0.058
103536	1185770	<5	<0.001	<0.005
103537	1185771	38	0.001	0.038
103538	1185772	8	<0.001	0.008
103539	1185773	17	<0.001	0.017
103540	1185774	19	<0.001	0.019
103541	1185775	13	<0.001	0.013
103542	1185776	14	<0.001	0.014
103543	1185777	7	<0.001	0.007
103544	1185778	28	<0.001	0.028
103545	1185779	22	<0.001	0.022
103546 Dup	1185779	34	<0.001	0.034
103547	1185780	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Thursday, April 26, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/17/2012
 Date Completed: 04/26/2012
 Job #: 201241199
 Reference: TL 12 244
 Sample #: 332

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
103548	1185781	11	<0.001	0.011
103549	1185782	19	<0.001	0.019
103550	1185783	24	<0.001	0.024
103551	1185784	109	0.003	0.109
103552	1185785	52	0.002	0.052
103553	1185786	19	<0.001	0.019
103554	1185787	31	<0.001	0.031
103555	1185788	30	<0.001	0.030
103556	1185789	64	0.002	0.064
103557 Dup	1185789	71	0.002	0.071
103558	1185790	1012	0.030	1.012
103559	1185791	22	<0.001	0.022
103560	1185792	19	<0.001	0.019
103561	1185793	6	<0.001	0.006
103562	1185794	<5	<0.001	<0.005
103563	1185795	38	0.001	0.038
103564	1185796	46	0.001	0.046
103565	1185797	119	0.003	0.119
103566	1185798	166	0.005	0.166
103567	1185799	55	0.002	0.055
103568 Dup	1185799	76	0.002	0.076
103569	1185800	<5	<0.001	<0.005
103570	1185801	212	0.006	0.212
103571	1185802	63	0.002	0.063
103572	1185803	13	<0.001	0.013
103573	1185804	5	<0.001	0.005
103574	1185805	6	<0.001	0.006
103575	1185806	12	<0.001	0.012
103576	1185807	6	<0.001	0.006
103577	1185808	10	<0.001	0.010

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Thursday, April 26, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/17/2012
 Date Completed: 04/26/2012
 Job #: 201241199
 Reference: TL 12 244
 Sample #: 332

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
103578	1185809	83	0.002	0.083
103579 Dup	1185809	25	<0.001	0.025
103580	1185810	253	0.007	0.253
103581	1185811	12	<0.001	0.012
103582	1185812	<5	<0.001	<0.005
103583	1185813	<5	<0.001	<0.005
103584	1185814	<5	<0.001	<0.005
103585	1185815	7	<0.001	0.007
103586	1185816	11	<0.001	0.011
103587	1185817	<5	<0.001	<0.005
103588	1185818	20	<0.001	0.020
103589	1185819	29	<0.001	0.029
103590 Dup	1185819	30	<0.001	0.030
103591	1185820	<5	<0.001	<0.005
103592	1185821	63	0.002	0.063
103593	1185822	161	0.005	0.161
103594	1185823	146	0.004	0.146
103595	1185824	19	<0.001	0.019
103596	1185825	6	<0.001	0.006
103597	1185826	<5	<0.001	<0.005
103598	1185827	<5	<0.001	<0.005
103599	1185828	<5	<0.001	<0.005
103600	1185829	<5	<0.001	<0.005
103601 Rep	1185829	<5	<0.001	<0.005
103602	1185830	5014	0.146	5.014
103603	1185831	5	<0.001	0.005
103604	1185832	10	<0.001	0.010
103605	1185833	62	0.002	0.062
103606	1185834	12	<0.001	0.012
103607	1185835	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Thursday, April 26, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/17/2012
 Date Completed: 04/26/2012
 Job #: 201241199
 Reference: TL 12 244
 Sample #: 332

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
103608	1185836	<5	<0.001	<0.005
103609	1185837	10	<0.001	0.010
103610	1185838	10	<0.001	0.010
103611	1185839	19	<0.001	0.019
103612 Dup	1185839	20	<0.001	0.020
103613	1185840	<5	<0.001	<0.005
103614	1185841	23	<0.001	0.023
103615	1185842	20	<0.001	0.020
103616	1185843	45	0.001	0.045
103617	1185844	68	0.002	0.068
103618	1185845	38	0.001	0.038
103619	1185846	28	<0.001	0.028
103620	1185847	80	0.002	0.080
103621	1185848	30	<0.001	0.030
103622	1185849	36	0.001	0.036
103623 Dup	1185849	62	0.002	0.062
103624	1185850	1220	0.036	1.220
103625	1185851	40	0.001	0.040
103626	1185852	21	<0.001	0.021
103627	1185853	58	0.002	0.058
103628	1185854	32	<0.001	0.032
103629	1185855	21	<0.001	0.021
103630	1185856	26	<0.001	0.026
103631	1185857	8	<0.001	0.008
103632	1185858	22	<0.001	0.022
103633	1185859	111	0.003	0.111
103634 Dup	1185859	59	0.002	0.059
103635	1185860	<5	<0.001	<0.005
103636	1185861	141	0.004	0.141
103637	1185862	15	<0.001	0.015

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Thursday, April 26, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/17/2012
 Date Completed: 04/26/2012
 Job #: 201241199
 Reference: TL 12 244
 Sample #: 332

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
103638	1185863	14	<0.001	0.014
103639	1185864	41	0.001	0.041
103640	1185865	108	0.003	0.108
103641	1185866	48	0.001	0.048
103642	1185867	8	<0.001	0.008
103643	1185868	26	<0.001	0.026
103644	1185869	26	<0.001	0.026
103645 Dup	1185869	38	0.001	0.038
103646	1185870	244	0.007	0.244
103647	1185871	49	0.001	0.049
103648	1185872	56	0.002	0.056
103649	1185873	57	0.002	0.057
103650	1185874	18	<0.001	0.018
103651	1185875	37	0.001	0.037
103652	1185876	41	0.001	0.041
103653	1185877	24	<0.001	0.024
103654	1185878	93	0.003	0.093
103655	1185879	41	0.001	0.041
103656 Dup	1185879	40	0.001	0.040
103657	1185880	<5	<0.001	<0.005
103658	1185881	60	0.002	0.060
103659	1185882	44	0.001	0.044
103660	1185883	11	<0.001	0.011
103661	1185884	12	<0.001	0.012
103662	1185885	40	0.001	0.040
103663	1185886	21	<0.001	0.021
103664	1185887	10	<0.001	0.010
103665	1185888	88	0.003	0.088
103666	1185889	10	<0.001	0.010
103667 Rep	1185889	22	<0.001	0.022

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Thursday, April 26, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/17/2012
 Date Completed: 04/26/2012
 Job #: 201241199
 Reference: TL 12 244
 Sample #: 332

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
103668	1185890	5033	0.147	5.033
103669	1185891	<5	<0.001	<0.005
103670	1185892	14	<0.001	0.014
103671	1185893	6	<0.001	0.006
103672	1185894	13	<0.001	0.013
103673	1185895	8	<0.001	0.008
103674	1185896	9	<0.001	0.009
103675	1185897	11	<0.001	0.011
103676	1185898	32	<0.001	0.032
103677	1185899	36	0.001	0.036
103678 Dup	1185899	45	0.001	0.045
103679	1185900	<5	<0.001	<0.005
103680	1185901	6	<0.001	0.006
103681	1185902	6	<0.001	0.006
103682	1185903	<5	<0.001	<0.005
103683	1185904	16	<0.001	0.016
103684	1185905	11	<0.001	0.011
103685	1185906	<5	<0.001	<0.005
103686	1185907	<5	<0.001	<0.005
103687	1185908	<5	<0.001	<0.005
103688	1185909	<5	<0.001	<0.005
103689 Dup	1185909	10	<0.001	0.010
103690	1185910	1216	0.035	1.216
103691	1185911	<5	<0.001	<0.005
103692	1185912	40	0.001	0.040
103693	1185913	25	<0.001	0.025
103694	1185914	110	0.003	0.110
103695	1185915	25	<0.001	0.025
103696	1185916	39	0.001	0.039
103697	1185917	41	0.001	0.041

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Thursday, April 26, 2012

Certificate of Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 04/17/2012
 Date Completed: 04/26/2012
 Job #: 201241199
 Reference: TL 12 244
 Sample #: 332

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
103698	1185918	<5	<0.001	<0.005
103699	1185919	2951	0.086	2.951
103700 Dup	1185919	2765	0.081	2.765
103701	1185920	<5	<0.001	<0.005
103702	1185921	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Friday, June 15, 2012


Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
133463	1185922	0.049	2	>10.00	7	310	2	11	5.96	<4	44	68	106	8.56	0.20	55	2.61	1941	<1	79	807	16	2.00	<5	<5	<10	212	6696	21	307	<10	45	168
133464	1185923	0.058	2	9.02	7	227	2	14	5.42	<4	46	63	111	9.62	0.10	49	2.53	1983	<1	76	795	11	1.67	5	<5	<10	170	5989	7	317	<10	44	140
133465	1185924	0.034	1	6.19	<2	129	2	14	5.39	<4	52	92	151	11.23	0.01	40	2.16	2544	<1	101	773	13	1.58	6	<5	<10	172	4635	12	309	<10	37	173
133466	1185925	0.011	<1	5.57	3	136	2	10	5.02	<4	46	90	103	8.75	0.05	35	2.25	1590	<1	85	782	10	1.14	<5	<5	<10	203	4409	<2	307	<10	36	130
133467	1185926	0.013	1	9.33	7	244	2	19	5.80	<4	51	90	93	9.91	0.11	47	3.02	1639	<1	82	827	12	1.92	<5	<5	<10	263	7015	8	314	<10	38	134
133468	1185927	0.031	1	7.92	4	156	2	17	5.15	<4	51	92	84	9.97	0.03	47	3.16	1444	<1	83	815	9	1.37	<5	<5	<10	240	7390	9	319	<10	37	114
133469	1185928	0.014	1	9.29	10	206	2	10	5.04	<4	50	87	80	10.14	0.09	50	3.30	1379	<1	64	867	8	1.66	5	<5	<10	267	7522	<2	335	41	41	113
133470	1185929	0.012	1	7.65	<2	232	2	6	4.54	<4	47	77	94	9.90	0.08	39	3.06	1393	<1	67	844	12	1.46	<5	<5	<10	273	5011	<2	319	<10	36	158
133471	1185930	0.258	2	3.62	406	>5000	<2	18	1.06	<4	5	17	31	2.92	<0.01	10	0.39	<100	10	15	115	24	2.19	17	<5	<10	153	1150	<2	19	40	11	31
133472	1185931	0.021	3	>10.00	9	558	2	5	5.82	<4	51	38	79	10.43	0.08	65	2.60	1628	4	56	912	14	3.30	<5	<5	<10	304	8757	7	360	<10	36	171
133473D	1185931	0.020	2	8.73	7	281	2	15	5.52	<4	47	32	78	10.16	0.16	52	2.90	1500	<1	52	905	16	2.30	<5	<5	<10	275	6095	3	355	<10	43	167
133474	1185932	0.018	1	7.96	2	242	2	3	5.29	<4	47	82	83	8.70	0.14	44	2.44	1325	1	73	777	9	1.69	<5	<5	<10	192	6491	5	321	<10	35	121
133475	1185933	0.020	<1	8.28	<2	214	2	18	6.07	<4	53	158	67	8.28	<0.01	35	2.50	1495	<1	91	724	10	1.37	<5	<5	<10	188	8449	2	321	<10	34	119
133476	1185934	0.020	1	>10.00	4	331	2	15	5.87	<4	59	158	97	7.07	<0.01	44	2.38	1434	1	104	774	10	1.73	<5	<5	<10	203	8510	14	302	<10	35	108
133477	1185935	0.015	1	7.75	<2	189	2	3	5.97	<4	55	71	88	8.62	<0.01	35	2.60	1597	<1	100	820	11	1.35	<5	<5	<10	196	7859	3	264	<10	34	125
133478	1185936	0.013	<1	6.71	5	144	2	15	6.33	<4	52	67	85	8.27	<0.01	29	2.50	1612	<1	100	785	9	1.26	<5	<5	<10	190	7384	7	248	<10	34	116
133479	1185937	0.020	1	9.40	5	264	<2	18	5.60	<4	61	84	85	7.94	<0.01	44	2.67	1690	<1	112	710	10	1.58	<5	<5	<10	189	8135	12	297	<10	33	135
133480	1185938	0.037	2	9.99	8	303	2	10	5.28	<4	55	101	116	9.42	<0.01	66	2.94	2325	<1	92	779	10	2.01	<5	<5	<10	214	9192	18	331	<10	36	149
133481	1185939	0.052	1	6.99	4	206	<2	24	5.77	<4	56	89	102	8.24	<0.01	42	2.64	1772	<1	114	765	8	1.31	<5	<5	<10	205	7994	15	289	<10	34	132
133482	1185940	0.006	1	8.25	8	575	<2	13	2.47	<4	16	50	21	3.35	<0.01	14	1.50	670	<1	31	603	9	1.43	<5	<5	<10	304	3275	14	115	18	19	58

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 15, 2012

Certificate of Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
133483	1185941	0.078	2	7.21	3	270	2	7	4.92	<4	53	49	90	10.97	<0.01	59	3.14	2402	<1	68	732	14	4.02	<5	<5	<10	128	5511	9	223	<10	38	230
133484D	1185941	0.089	3	>10.00	9	505	2	18	5.52	<4	53	56	90	11.09	<0.01	77	3.36	2465	5	71	778	15	4.88	<5	<5	<10	170	6419	<2	230	<10	43	222
133485	1185942	0.113	2	7.75	3	345	<2	14	6.04	<4	30	46	43	7.37	<0.01	50	2.89	2418	<1	63	803	10	2.39	<5	<5	<10	174	6534	15	213	<10	37	92
133486	1185943	0.030	1	9.01	7	362	2	15	5.09	<4	36	44	19	7.46	<0.01	78	2.92	2460	<1	61	872	7	1.72	<5	<5	<10	154	7238	5	223	<10	40	101
133487	1185944	0.082	2	6.80	4	346	2	2	6.33	<4	36	62	59	8.11	0.11	70	2.73	2153	3	85	784	11	2.29	<5	<5	<10	172	7506	11	245	<10	30	107
133488	1185945	0.037	2	6.88	7	368	2	21	5.71	<4	50	78	61	8.17	0.12	60	2.60	2214	3	86	823	11	2.41	<5	<5	<10	171	9213	7	307	<10	31	114
133489	1185946	0.051	<1	5.23	8	201	<2	11	>10.00	<4	18	26	9	6.11	0.50	42	4.96	3704	<1	37	431	12	1.35	<5	<5	<10	215	4019	37	163	<10	25	70
133490	1185947	0.035	1	6.37	2	196	2	17	6.21	<4	52	73	87	9.83	0.31	53	2.93	1953	<1	82	964	12	1.76	<5	<5	<10	237	8306	9	350	<10	41	134
133491	1185948	0.023	1	8.34	4	279	2	16	5.16	<4	53	75	84	10.59	0.06	66	3.12	1368	<1	83	948	9	1.47	6	<5	<10	256	8917	2	352	<10	42	129
133492	1185949	0.060	2	6.26	3	267	2	8	5.19	<4	51	59	93	10.33	<0.01	50	2.61	1336	<1	63	903	11	1.84	<5	<5	<10	198	8600	<2	348	<10	33	124
133493	1185950	4.335	2	7.11	376	1732	<2	2	2.45	<4	12	110	76	3.52	0.20	18	1.32	468	11	51	799	29	2.22	32	<5	<10	214	2214	6	125	<10	17	208
133494	1185951	0.022	<1	6.30	3	240	2	13	5.27	<4	49	77	88	9.62	<0.01	43	2.98	1335	<1	84	909	11	1.24	<5	<5	<10	235	5106	<2	320	<10	38	177
133495D	1185951	0.037	1	7.94	<2	299	2	21	5.36	<4	48	76	86	9.50	0.03	47	2.99	1307	<1	79	897	9	1.54	<5	<5	<10	248	4703	4	317	<10	39	175
133496	1185952	0.067	2	9.79	5	369	2	15	5.55	<4	45	71	78	9.08	0.16	58	2.57	1336	2	72	833	13	2.24	<5	<5	<10	237	6319	13	276	<10	32	124
133497	1185953	0.035	1	8.92	2	241	2	7	5.79	<4	48	71	100	9.71	0.04	53	3.08	1542	<1	81	779	13	1.87	<5	<5	<10	211	4955	13	300	<10	36	231
133498	1185954	0.047	1	8.38	5	189	2	12	6.06	<4	49	69	98	10.00	0.12	47	2.95	1460	<1	76	812	14	1.65	5	<5	<10	201	6034	5	321	<10	38	147
133499	1185955	0.021	1	4.96	4	234	2	15	4.88	<4	56	71	111	9.52	<0.01	54	1.95	1851	<1	82	830	15	1.85	<5	<5	<10	232	8163	10	353	<10	31	148
133500	1185956	0.026	1	5.44	2	247	2	17	4.85	<4	57	73	104	9.55	<0.01	55	1.97	1896	<1	84	868	13	1.87	<5	<5	<10	232	8566	3	355	<10	32	157
133501	1185957	0.046	1	6.51	2	173	2	16	4.91	<4	52	61	91	9.46	0.18	48	1.94	1838	<1	72	873	14	1.91	<5	<5	<10	253	7658	<2	306	<10	38	144
133502	1185958	0.162	1	7.04	3	180	2	10	4.30	<4	56	80	97	10.00	<0.01	55	2.08	1797	<1	101	929	13	1.52	<5	<5	<10	209	7539	2	367	<10	36	154

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 15, 2012

Certificate of Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
133503	1185959	0.044	1	7.79	10	277	2	14	7.96	<4	47	48	63	9.50	0.34	65	3.78	2748	<1	60	846	9	1.89	<5	<5	<10	185	7729	26	306	<10	38	142
133504	1185960	<0.005	1	6.59	8	491	<2	7	2.33	<4	15	49	21	3.35	0.17	9	1.46	671	<1	30	592	4	0.84	<5	<5	<10	290	3122	4	114	16	17	52
133505	1185961	0.044	2	8.93	3	259	2	19	4.27	<4	58	70	91	9.92	0.26	75	2.93	1929	<1	101	942	15	1.91	<5	<5	<10	189	7617	<2	340	<10	38	171
133506D	1185961	0.104	1	7.83	<2	216	2	11	4.19	<4	59	74	92	9.96	0.36	72	2.91	1924	<1	113	938	15	1.83	6	<5	<10	180	7345	9	338	<10	37	176
133507	1185962	0.044	1	9.01	<2	296	2	23	5.41	<4	54	72	87	9.20	0.09	69	2.84	1979	1	100	921	12	1.99	<5	<5	<10	212	5323	8	330	<10	40	129
133508	1185963	0.082	3	>10.00	2	526	2	13	5.31	<4	55	76	96	10.70	0.24	87	2.48	2337	7	84	933	16	3.32	<5	<5	<10	248	8573	<2	353	<10	37	152
133509	1185964	0.674	3	>10.00	4	346	2	13	5.95	<4	47	72	79	9.13	0.25	56	2.93	1712	3	85	902	11	2.34	5	<5	<10	231	6411	<2	311	14	41	138
133510	1185965	3.872	2	7.09	2	203	2	10	4.81	<4	45	66	95	9.32	0.18	42	2.68	1229	<1	81	845	13	1.86	<5	<5	<10	177	5646	<2	309	<10	38	117
133511	1185966	0.055	1	8.06	6	244	2	16	6.06	<4	50	59	99	10.13	0.17	49	2.95	2142	<1	69	976	11	1.78	<5	<5	<10	220	7768	7	341	<10	39	136
133512	1185967	0.068	2	5.87	<2	282	2	13	5.40	<4	57	71	91	10.38	<0.01	64	2.25	1733	<1	81	873	13	1.93	<5	<5	<10	235	8872	8	351	<10	29	159
133513	1185968	0.049	2	6.03	4	249	2	15	3.84	<4	50	67	103	9.19	0.35	50	1.60	1951	4	104	749	13	3.11	<5	<5	<10	225	7026	6	258	<10	25	262
133514	1185969	0.026	1	6.62	<2	163	2	8	6.66	<4	49	53	107	10.00	0.20	38	2.37	1831	<1	69	1009	8	1.41	<5	<5	<10	229	6829	5	315	<10	42	169
133515	1185970	1.175	2	6.25	27	641	<2	8	1.54	<4	14	50	552	3.75	0.11	8	1.15	580	27	35	659	70	1.45	5	<5	<10	253	2217	<2	112	26	16	99
133516	1185971	0.085	<1	7.17	4	161	<2	6	5.42	<4	25	56	42	5.20	0.54	51	1.45	970	2	38	504	5	0.82	<5	<5	<10	100	3089	7	160	<10	21	87
133517D	1185971	0.109	<1	3.19	31	10	3	26	4.63	5	39	50	69	8.59	<0.01	39	2.49	1603	<1	71	839	22	0.68	5	15	<10	160	4854	3	260	<10	35	163
133518	1185972	0.078	<1	3.35	29	6	2	21	5.39	4	39	55	79	7.81	<0.01	40	2.34	1498	59	72	714	31	0.79	5	12	<10	173	4064	3	258	<10	30	160
133519	1185973	0.341	<1	6.14	3	188	2	10	5.76	<4	41	71	97	8.96	<0.01	42	2.78	1391	<1	73	827	12	1.34	<5	<5	<10	170	3666	15	299	<10	33	120
133520	1185974	0.011	2	>10.00	6	432	3	6	5.65	<4	47	67	105	9.42	0.22	70	2.44	1335	3	54	856	12	2.08	6	<5	<10	236	6954	6	324	<10	29	118
133521	1185975	0.010	2	9.99	2	235	2	20	5.39	<4	47	67	109	10.07	0.23	73	2.93	1383	<1	70	929	12	1.80	<5	<5	<10	262	6110	6	341	<10	38	117
133522	1185976	<0.005	<1	6.40	5	95	2	16	5.37	<4	45	59	102	9.79	0.15	59	2.83	1355	<1	59	902	11	1.09	<5	<5	<10	235	4614	6	335	<10	36	118

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 15, 2012


Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
133523	1185977	<0.005	1	7.97	9	159	2	24	5.35	<4	55	50	133	10.64	0.10	65	2.82	1553	<1	67	1014	10	1.30	<5	<5	<10	334	8969	<2	363	<10	38	122
133524	1185978	<0.005	2	8.60	5	196	<2	14	5.15	<4	46	82	89	9.45	<0.01	85	3.05	1445	<1	69	838	13	1.57	<5	<5	<10	260	6025	4	330	<10	33	106
133525	1185979	<0.005	<1	5.61	2	61	2	6	5.17	<4	46	108	104	8.94	0.18	63	2.90	1338	<1	84	779	11	0.90	<5	<5	<10	239	5395	3	284	<10	30	112
133526	1185980	<0.005	1	7.64	10	540	<2	11	2.44	<4	15	49	22	3.35	0.14	13	1.49	670	<1	31	591	8	0.97	<5	<5	<10	299	3278	9	116	19	18	56
133527	1185981	0.010	2	7.84	9	329	2	15	6.30	<4	51	100	87	9.42	<0.01	81	2.61	1502	3	97	708	10	2.27	5	<5	<10	340	7507	5	299	<10	25	119
133528R	1185981	0.006	<1	9.86	4	<1	2	5	6.26	<4	51	100	88	9.56	0.41	73	3.13	1540	<1	100	760	11	1.58	<5	<5	<10	318	7406	5	303	<10	32	122
133529	1185982	0.009	1	8.33	7	137	2	15	5.48	<4	49	74	84	9.34	0.30	76	3.22	1368	<1	80	812	7	1.13	<5	<5	<10	321	5905	<2	307	<10	33	121
133530	1185983	0.170	1	6.58	<2	138	2	6	4.72	<4	49	68	145	9.70	<0.01	64	3.23	1307	<1	71	865	10	1.39	5	<5	<10	183	6515	<2	317	<10	32	141
133531	1185984	0.176	1	7.09	7	321	2	16	4.97	<4	49	66	107	9.56	0.20	59	3.26	1334	<1	78	880	14	1.36	<5	<5	<10	151	5096	7	330	<10	36	129
133532	1185985	0.072	2	5.67	7	295	2	18	5.85	<4	49	75	97	9.62	<0.01	59	2.69	1481	<1	73	743	11	1.26	<5	<5	<10	212	6825	2	329	<10	28	134
133533	1185986	0.015	1	7.81	8	187	2	25	6.14	<4	48	75	105	9.90	0.02	55	3.16	1541	<1	72	813	13	1.33	<5	<5	<10	212	6476	8	334	<10	34	137
133534	1185987	0.009	<1	7.27	5	161	<2	18	5.57	<4	46	76	81	9.10	0.17	54	2.87	1334	3	70	762	10	1.31	<5	<5	<10	199	5811	<2	315	<10	33	116
133535	1185988	0.442	2	9.86	2	214	2	26	6.33	<4	50	83	127	10.28	0.39	57	2.98	1494	2	82	921	16	1.98	<5	<5	<10	254	6741	8	365	<10	38	125
133536	1185989	0.147	2	9.74	4	260	2	23	5.97	<4	49	84	111	9.74	0.22	64	3.27	1686	<1	82	860	14	1.87	<5	<5	<10	227	6693	13	337	<10	37	134
133537	1185990	0.228	2	5.85	398	>5000	<2	6	1.23	<4	5	18	30	2.85	0.03	17	0.46	<100	11	12	135	22	2.30	18	<5	<10	180	1394	<2	19	39	13	26
133538	1185991	0.059	2	>10.00	8	346	2	20	6.08	<4	47	80	102	8.92	0.20	66	3.11	1659	2	97	773	13	2.11	<5	<5	<10	233	6136	9	289	<10	34	143
133539D	1185991	0.022	1	8.26	<2	251	2	17	5.85	<4	46	82	104	8.85	0.08	58	3.04	1644	<1	101	759	14	1.77	<5	<5	<10	215	5341	3	289	<10	32	144
133540	1185992	<0.005	2	9.96	7	285	2	18	5.96	<4	50	75	91	8.93	0.14	54	2.62	1264	<1	84	848	12	1.78	<5	<5	<10	217	5643	3	328	<10	36	114
133541	1185993	0.018	1	7.26	7	173	2	10	6.10	<4	53	119	121	8.80	0.23	44	2.27	1724	<1	96	856	11	1.12	<5	<5	<10	209	6240	2	339	<10	34	110
133542	1185994	0.011	<1	6.59	5	115	2	8	6.11	<4	51	117	92	9.07	0.12	38	2.23	1869	<1	95	810	10	1.01	5	<5	<10	203	5799	12	325	<10	32	110

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 15, 2012

Certificate of Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
133543	1185995	0.024	1	4.68	3	318	2	12	5.64	<4	55	122	109	9.44	0.24	53	1.97	2074	<1	95	700	12	1.36	<5	<5	<10	206	7800	5	341	<10	23	126
133544	1185996	0.034	1	5.98	4	182	2	5	6.00	<4	55	127	108	9.75	<0.01	51	2.28	2131	<1	102	799	17	0.94	5	<5	<10	209	6914	11	356	<10	30	137
133545	1185997	0.059	1	5.56	<2	316	2	16	4.91	<4	54	121	107	8.76	<0.01	74	2.32	2019	<1	87	776	10	1.45	<5	<5	<10	242	8604	14	359	<10	24	160
133546	1185998	0.078	1	7.07	3	244	2	14	6.18	<4	52	90	114	9.92	<0.01	59	2.72	1536	<1	88	893	15	1.20	<5	<5	<10	204	7408	<2	358	<10	34	129
133547	1185999	0.087	2	7.46	2	250	2	11	6.83	<4	50	87	83	9.69	<0.01	45	2.49	1739	2	87	846	10	1.72	<5	<5	<10	209	7608	10	341	<10	32	121
133548	1186000	<0.005	1	7.50	8	608	<2	15	2.56	<4	16	52	24	3.40	0.30	18	1.44	684	<1	31	555	12	1.51	<5	<5	<10	309	3366	3	118	17	17	58
133549	1304001	0.048	2	>10.00	11	300	2	21	6.72	<4	53	122	100	9.85	0.25	53	2.90	1716	<1	88	749	14	2.04	5	<5	<10	228	7527	4	338	<10	33	123
133550D	1304001	0.022	1	9.53	4	240	2	18	6.58	<4	52	124	101	9.84	0.12	48	2.86	1698	<1	95	739	13	1.84	<5	<5	<10	216	7134	4	336	<10	32	127
133551	1304002	0.142	2	>10.00	10	318	2	8	6.32	<4	59	131	130	7.81	0.17	50	2.28	1454	<1	96	779	12	1.72	<5	<5	<10	227	6836	12	355	<10	32	100
133552	1304003	0.177	2	>10.00	90	298	2	5	5.67	<4	47	88	78	9.08	0.09	56	2.60	2126	<1	82	732	12	2.71	6	<5	<10	221	4986	7	276	<10	30	199
133553	1304004	0.046	2	6.55	9	221	<2	7	5.88	<4	45	85	82	8.54	0.10	48	2.77	1650	<1	83	695	19	1.65	<5	<5	<10	247	6481	3	294	<10	26	163
133554	1304005	0.037	<1	6.16	3	96	2	17	6.04	<4	47	87	113	9.56	0.37	37	3.12	1384	<1	72	724	19	1.25	<5	<5	<10	245	4754	9	329	<10	30	149
133555	1304006	0.096	2	6.24	8	228	2	14	6.29	<4	50	105	123	9.46	0.02	46	2.84	1488	<1	69	698	23	1.92	<5	<5	<10	249	6405	10	323	<10	25	176
133556	1304007	0.178	1	6.64	5	226	2	7	5.26	<4	42	91	97	8.11	<0.01	53	2.93	1401	<1	89	631	21	1.62	<5	<5	<10	213	5782	4	268	<10	24	407
133557	1304008	0.032	<1	5.78	13	474	<2	11	2.48	<4	10	45	38	2.48	<0.01	43	1.24	608	3	83	285	27	1.01	<5	<5	<10	166	1788	12	42	<10	6	146
133558	1304009	0.119	1	7.59	20	579	2	12	3.75	5	6	36	42	2.53	0.03	40	1.63	941	3	64	282	13	1.56	<5	<5	<10	167	1506	17	33	15	8	1347
133559	1304010	4.332	3	7.22	348	1732	2	7	2.43	<4	12	107	78	3.44	0.07	20	1.29	461	11	50	755	28	1.98	34	<5	<10	212	2264	6	122	<10	17	220
133560	1304011	0.062	1	7.32	13	671	2	10	4.30	<4	5	32	9	2.48	<0.01	47	1.91	1184	<1	49	299	12	1.93	<5	<5	<10	187	1677	19	33	<10	7	82
133561D	1304011	0.050	1	9.52	8	718	<2	12	4.45	<4	5	34	8	2.51	0.27	52	2.02	1193	3	53	327	12	2.20	<5	<5	<10	198	1772	18	33	<10	9	78
133562	1304012	0.032	1	>10.00	10	649	<2	17	2.83	<4	6	56	8	2.01	0.06	55	1.49	641	9	100	350	7	1.85	5	<5	<10	185	1727	9	34	<10	9	35

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 15, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
133563	1304013	0.027	2	>10.00	11	765	<2	11	3.39	<4	5	34	3	2.03	0.16	55	1.69	714	4	57	357	9	2.16	5	<5	<10	208	1762	16	33	<10	10	37
133564	1304014	0.025	1	9.80	7	656	2	8	2.35	<4	6	41	8	1.88	<0.01	45	1.18	444	6	72	348	10	1.79	<5	<5	<10	198	1740	<2	36	<10	9	36
133565	1304015	0.016	1	7.87	11	578	2	9	2.27	<4	7	36	9	1.84	0.04	41	1.08	420	3	58	303	10	1.62	<5	<5	<10	190	1776	4	38	<10	7	43
133566	1304016	0.012	2	7.51	10	588	<2	13	2.24	<4	6	38	8	1.83	0.07	41	1.04	421	3	62	285	10	1.60	<5	<5	<10	196	1751	9	38	<10	6	42
133567	1304017	0.233	<1	7.24	4	461	<2	11	3.04	<4	16	38	59	2.73	0.30	20	1.48	664	<1	57	312	18	1.87	<5	<5	<10	201	1520	16	34	<10	7	318
133568	1304018	0.047	2	6.73	20	427	2	7	2.34	<4	27	61	127	4.48	0.03	23	1.26	585	2	99	325	35	3.20	5	<5	<10	183	1846	<2	75	<10	7	892
133569	1304019	0.050	2	6.27	30	401	2	13	2.01	<4	35	75	117	3.85	<0.01	21	1.05	540	3	105	426	26	2.78	<5	<5	<10	175	2127	6	88	14	7	1228
133570	1304020	0.005	1	7.26	10	555	<2	12	2.47	<4	16	51	22	3.38	0.07	14	1.47	678	<1	32	566	9	0.87	<5	<5	<10	303	3223	13	117	18	17	61
133571	1304021	0.046	2	6.88	26	469	2	15	3.19	4	25	57	100	4.12	<0.01	27	1.30	907	2	83	523	26	3.10	<5	<5	<10	195	2396	7	90	16	9	1474
133572D	1304021	0.043	2	7.65	24	456	2	10	3.13	4	24	59	98	4.10	<0.01	26	1.34	892	3	88	536	24	3.27	<5	<5	<10	192	2346	4	88	17	9	1471
133573	1304022	0.060	2	9.66	139	385	2	4	2.81	<4	19	49	49	5.83	0.22	36	1.88	1263	3	98	619	13	2.95	<5	<5	<10	168	3044	3	70	<10	14	148
133574	1304023	0.114	1	9.34	12	413	2	17	3.25	<4	24	86	32	3.87	0.09	38	1.99	824	4	130	744	14	1.89	6	<5	<10	184	3556	10	91	<10	12	98
133575	1304024	0.013	2	>10.00	12	537	2	9	3.56	<4	19	70	27	3.07	0.10	37	1.80	916	5	102	676	15	1.70	<5	<5	<10	198	3685	7	79	<10	12	99
133576	1304025	0.082	1	>10.00	11	578	2	11	3.42	<4	22	97	35	3.91	0.01	39	1.88	990	9	133	690	12	1.91	<5	<5	<10	179	3963	11	91	<10	13	87
133577	1304026	0.007	1	6.83	5	579	<2	4	2.06	<4	8	47	12	1.92	<0.01	27	0.98	511	4	74	291	10	1.20	<5	<5	<10	173	1916	<2	41	<10	6	51
133578	1304027	0.049	1	6.19	3	572	<2	7	2.47	<4	6	48	31	2.18	<0.01	31	1.12	651	6	84	253	12	1.58	<5	<5	<10	162	1759	9	38	<10	7	138
133579	1304028	2.422	2	5.10	7	399	2	4	4.02	<4	47	258	74	7.02	<0.01	64	2.15	1371	3	198	1116	13	2.43	<5	<5	<10	157	8164	3	176	<10	15	236
133580	1304029	0.039	1	6.79	2	358	2	11	4.33	<4	53	321	45	6.57	<0.01	55	2.04	1399	<1	196	1210	13	1.47	5	<5	<10	187	8005	3	195	<10	21	129
133581	1304030	1.292	2	6.47	19	743	<2	13	1.68	<4	14	53	553	3.72	<0.01	15	1.11	582	25	38	571	72	1.48	5	<5	<10	263	2403	3	112	26	14	103
133582	1304031	0.029	1	6.21	6	390	2	12	4.55	<4	54	319	48	7.14	<0.01	68	2.00	1677	3	219	1082	13	1.53	<5	<5	<10	196	8615	4	191	<10	19	127

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 15, 2012

Certificate of Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
133583D	1304031	0.062	2	5.99	6	446	2	17	4.56	<4	53	313	47	7.02	<0.01	71	1.89	1662	3	213	1035	12	1.77	<5	<5	<10	202	8686	<2	189	<10	18	141
133584	1304032	0.077	2	6.15	7	482	2	8	4.03	<4	59	320	58	5.98	<0.01	55	1.53	1197	4	210	1051	13	2.49	<5	<5	<10	199	8308	4	188	<10	16	164
133585	1304033	0.021	1	>10.00	6	461	2	18	5.52	<4	67	382	64	7.46	<0.01	88	2.57	1315	<1	236	1625	13	2.01	<5	<5	<10	275	8867	3	238	12	26	157
133586	1304034	0.017	1	9.13	<2	361	2	11	6.65	<4	51	303	45	7.18	0.11	45	2.89	1277	<1	161	1229	11	1.51	<5	<5	<10	304	9357	<2	188	<10	25	136
133587	1304035	0.014	1	8.35	4	379	2	<1	5.51	<4	49	306	49	6.32	<0.01	49	2.68	1130	<1	182	1213	9	1.41	<5	<5	<10	309	7775	11	192	<10	24	115
133588	1304036	0.014	1	9.67	8	426	2	6	5.39	<4	49	289	49	6.17	0.09	51	2.65	1126	<1	177	1258	8	1.62	<5	<5	<10	302	8188	14	180	<10	25	111
133589	1304037	0.017	1	7.59	7	254	2	13	5.62	<4	49	296	49	6.09	0.05	37	2.52	1187	<1	191	1099	9	1.03	<5	<5	<10	236	7888	12	181	<10	24	118
133590	1304038	0.085	1	6.15	3	379	<2	6	5.03	<4	54	317	56	6.21	<0.01	54	2.23	1233	<1	214	1145	9	1.25	<5	<5	<10	277	7666	13	192	<10	20	140
133591	1304039	0.014	2	5.58	<2	424	2	11	5.10	<4	55	340	53	7.06	<0.01	58	2.18	1421	<1	214	1155	11	1.85	<5	<5	<10	311	8183	9	203	<10	17	165
133592	1304040	<0.005	1	6.49	7	510	<2	10	2.38	<4	15	52	21	3.37	0.11	11	1.44	677	<1	31	565	10	0.93	<5	<5	<10	297	3187	6	117	17	17	56
133593	1304041	0.019	<1	7.40	8	256	2	20	4.77	<4	48	314	50	6.43	0.26	53	2.54	1271	1	222	1245	10	0.87	<5	<5	<10	253	6215	<2	183	<10	23	144
133594R	1304041	0.035	<1	9.01	8	129	2	5	5.00	<4	50	315	50	6.61	0.16	59	2.60	1344	<1	206	1309	8	1.39	6	<5	<10	257	7458	12	187	<10	24	174
133595	1304042	0.021	2	6.94	46	401	2	10	5.75	<4	52	320	107	6.25	0.22	49	1.93	1487	5	226	1074	43	1.66	<5	<5	<10	281	9208	11	185	<10	19	454
133596	1304043	0.016	2	6.33	7	537	2	10	5.40	<4	53	317	55	6.21	<0.01	57	1.65	1459	5	220	1073	11	2.00	<5	<5	<10	321	9334	10	182	14	17	144
133597	1304044	0.025	1	6.57	13	703	2	10	2.99	<4	19	105	32	3.31	0.29	62	1.16	748	2	99	605	12	1.77	<5	<5	<10	226	4370	7	83	<10	9	77
133598	1304045	0.023	2	>10.00	11	895	2	23	3.32	<4	23	129	40	3.24	<0.01	67	1.45	706	9	128	817	9	2.40	5	<5	<10	254	4832	4	90	<10	16	75
133599	1304046	0.348	3	7.21	5	639	2	18	5.44	<4	33	192	117	5.16	<0.01	54	1.89	1389	6	145	825	14	3.02	5	<5	<10	262	6007	3	136	10	14	278
133600	1304047	0.070	2	7.57	10	524	2	9	5.00	<4	52	298	49	6.10	<0.01	67	2.01	1887	4	196	989	13	3.05	6	<5	<10	207	8397	8	184	11	18	188
133601	1304048	0.014	2	9.48	9	516	2	10	5.56	<4	54	330	48	5.40	0.04	68	2.08	1614	5	202	1168	15	1.90	5	<5	<10	225	10158	14	195	26	23	135
133602	1304049	0.023	2	9.15	6	626	2	15	5.25	<4	50	305	47	6.55	0.03	68	2.05	1617	5	192	1173	13	2.25	<5	<5	<10	220	9705	8	188	20	21	137

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 15, 2012


Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
133603	1304050	0.222	2	2.24	416	>5000	<2	3	0.95	<4	5	17	32	2.97	0.09	6	0.33	<100	9	14	103	27	1.80	20	<5	<10	164	1065	<2	18	44	10	29
133604	1304051	0.026	<1	7.24	9	749	2	4	5.14	<4	43	254	51	6.65	<0.01	50	2.55	1828	<1	183	1096	14	1.81	5	<5	<10	224	7627	19	160	<10	21	196
133605D	1304051	0.025	1	7.67	6	728	2	12	5.07	<4	43	246	49	6.44	0.14	50	2.51	1768	<1	178	1052	16	1.86	5	<5	<10	224	7431	13	157	<10	21	190
133606	1304052	0.024	1	9.60	4	529	2	7	4.74	<4	48	320	47	6.50	0.05	57	2.01	1571	<1	195	1268	12	1.56	<5	<5	<10	261	6995	6	190	<10	25	119
133607	1304053	0.025	2	5.99	6	408	2	10	5.07	<4	50	305	52	6.91	<0.01	50	1.89	1765	2	196	1088	6	1.65	5	<5	<10	235	8264	10	182	<10	18	139
133608	1304054	0.020	1	6.08	4	369	2	8	5.03	<4	52	321	46	6.42	0.16	53	1.72	1674	2	212	1108	10	1.54	<5	<5	<10	205	8832	3	189	11	18	113
133609	1304055	0.064	2	5.16	5	400	<2	17	4.65	<4	51	322	59	6.56	<0.01	55	1.66	1563	3	204	1060	11	2.29	<5	<5	<10	185	9100	4	189	15	17	209
133610	1304056	0.070	2	5.87	<2	417	2	18	4.77	<4	53	313	60	6.56	<0.01	58	1.78	1573	2	193	1066	11	2.33	<5	<5	<10	182	8780	10	187	13	17	210
133611	1304057	0.030	2	6.05	3	413	2	<1	5.12	<4	51	310	57	6.44	<0.01	47	1.81	1725	2	188	1026	13	2.16	<5	<5	<10	182	8950	6	180	<10	18	155
133612	1304058	0.022	2	7.56	2	582	2	13	5.73	<4	54	326	61	6.91	<0.01	62	1.71	1828	3	181	1049	13	2.62	<5	<5	<10	211	9749	8	195	<10	18	119
133613	1304059	0.050	1	9.69	2	373	2	11	4.64	<4	47	313	47	6.16	0.25	52	2.01	1516	2	185	1244	12	1.75	<5	<5	<10	174	7999	<2	187	14	24	163
133614	1304060	<0.005	2	9.23	8	643	2	16	2.67	<4	16	53	21	3.39	0.03	22	1.49	678	<1	31	579	10	1.82	<5	<5	<10	320	3461	13	117	18	18	55
133615	1304061	0.054	<1	6.88	7	286	<2	4	6.17	<4	52	300	58	7.00	<0.01	43	2.43	2102	<1	186	1123	7	1.46	<5	<5	<10	150	7981	8	178	<10	23	109
133616D	1304061	0.043	2	9.37	5	383	2	15	6.23	<4	52	291	57	6.83	<0.01	50	2.42	2080	<1	177	1169	7	2.04	<5	<5	<10	167	8561	5	176	<10	24	105
133617	1304062	0.063	2	>10.00	6	436	2	16	5.31	<4	50	308	48	6.95	0.08	50	2.38	1828	4	186	1134	13	2.95	<5	<5	<10	168	8856	6	175	<10	26	114
133618	1304063	0.080	1	>10.00	10	205	2	13	5.11	<4	42	255	30	5.91	0.07	43	2.21	1665	<1	164	940	13	2.69	<5	<5	<10	164	7342	23	160	10	20	157
133619	1304064	0.027	<1	7.45	3	321	2	14	4.28	<4	33	169	45	3.86	0.05	44	1.49	949	<1	127	653	12	1.55	<5	<5	<10	212	4698	9	134	<10	11	84
133620	1304065	0.023	<1	6.83	2	230	2	2	5.03	<4	33	158	36	4.02	0.22	61	2.16	1225	<1	144	908	10	1.78	<5	<5	<10	192	5429	16	144	<10	14	103
133621	1304066	0.173	2	>10.00	4	260	2	12	5.12	<4	32	158	84	4.39	0.24	62	2.37	1451	<1	124	1003	15	3.00	5	<5	<10	215	5431	17	143	<10	20	162
133622	1304067	0.023	<1	6.44	6	285	<2	7	4.64	<4	30	153	38	3.30	<0.01	46	1.57	1106	<1	125	639	15	1.85	<5	<5	<10	222	3983	3	127	<10	11	55

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By:  Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 15, 2012


Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
133623	1304068	0.013	1	>10.00	<2	245	2	27	5.31	<4	42	187	38	4.79	0.09	74	2.66	1173	<1	142	1142	12	2.26	5	<5	<10	257	7059	7	167	<10	20	110
133624	1304069	0.034	<1	8.02	9	254	2	11	4.86	<4	52	331	58	5.88	<0.01	58	1.81	1389	<1	201	1178	12	2.00	6	<5	<10	240	8563	<2	194	<10	18	117
133625	1304070	4.775	1	8.50	356	1435	<2	7	2.41	<4	11	109	75	3.36	0.21	23	1.33	448	6	48	739	30	2.75	33	<5	<10	204	1999	8	118	10	17	196
133626	1304071	0.060	<1	>10.00	7	319	2	5	4.19	<4	36	221	105	4.93	0.34	60	1.69	1124	<1	162	1072	11	2.57	<5	<5	<10	249	6508	5	145	<10	19	172
133627D	1304071	0.050	<1	7.63	9	293	2	10	3.92	<4	35	215	102	4.80	0.02	51	1.58	1068	<1	162	1038	10	1.96	6	<5	<10	232	5857	<2	141	<10	17	168
133628	1304072	0.043	<1	8.12	11	364	<2	11	1.86	<4	4	26	11	1.57	0.17	41	0.83	287	<1	44	327	9	1.23	<5	<5	<10	248	1610	4	33	<10	7	42
133629	1304073	0.010	<1	8.44	6	329	2	6	2.01	<4	3	25	14	1.31	0.23	35	0.69	238	<1	36	300	10	1.60	<5	<5	<10	246	1351	<2	27	<10	8	30
133630	1304074	0.017	<1	8.01	4	309	<2	13	2.65	<4	8	50	24	2.19	0.12	37	0.98	521	<1	60	412	10	1.56	6	<5	<10	207	1951	<2	48	<10	8	58
133631	1304075	0.021	<1	8.92	5	183	2	14	4.64	<4	22	114	26	3.88	0.11	58	1.59	1136	<1	96	584	9	1.63	<5	<5	<10	251	3340	13	93	<10	12	80
133632	1304076	0.015	<1	6.78	10	217	2	<1	5.01	<4	24	127	31	4.23	<0.01	62	1.43	1259	<1	102	555	9	1.43	<5	<5	<10	261	3785	21	106	<10	10	88
133633	1304209	0.037	<1	6.25	<2	182	2	21	5.43	<4	34	154	50	6.06	<0.01	59	2.08	1766	<1	123	668	15	2.05	7	<5	<10	218	4661	9	138	<10	11	152
133634	1304210	IS																															
133635	1304211	0.043	<1	6.34	7	215	2	5	5.15	<4	27	154	38	4.81	<0.01	64	1.95	1787	<1	104	604	10	2.08	5	<5	<10	177	4479	16	131	<10	11	142
133636	1304212	0.055	1	7.38	10	210	2	7	5.61	<4	37	145	37	4.73	<0.01	60	2.12	1969	<1	127	879	14	2.75	<5	<5	<10	173	6101	19	156	<10	13	107
133637	1304213	0.009	<1	>10.00	7	185	2	13	5.12	<4	41	162	47	5.51	0.17	68	2.46	1715	<1	130	1008	12	2.35	5	<5	<10	184	6874	16	168	<10	17	104
133638D	1304213	0.039	<1	>10.00	12	171	2	11	5.03	<4	41	161	47	5.52	0.26	61	2.62	1729	<1	131	1116	9	1.93	<5	<5	<10	173	6954	15	167	<10	19	105
133639	1304214	0.018	<1	>10.00	6	208	2	9	5.72	<4	41	158	44	4.12	0.39	64	2.19	1181	<1	121	1156	10	1.92	<5	<5	<10	215	6845	18	165	<10	19	89
133640	1304215	0.441	1	5.85	5	172	2	10	6.18	11	47	120	151	8.93	<0.01	38	2.51	2050	<1	107	939	17	5.34	5	<5	<10	166	4943	14	131	26	15	1816
133641	1304216	0.137	2	7.84	8	194	2	16	6.46	12	42	120	146	8.78	<0.01	48	2.62	2064	<1	100	969	16	5.71	8	<5	<10	175	5041	20	134	26	17	2005
133642	1304217	0.101	<1	>10.00	7	208	2	8	5.58	<4	36	169	43	5.32	0.11	70	2.01	1518	<1	128	1126	15	2.05	6	<5	<10	179	6285	6	157	<10	19	158

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 15, 2012


Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
133643	1304218	4.594	8	5.61	2	<1	2	20	6.64	4	76	71	361	15.57	0.06	31	3.62	3339	<1	99	559	23	8.38	<5	<5	<10	108	3047	11	101	23	12	202
133644	1304219	0.107	1	5.09	4	153	2	<1	5.20	<4	41	190	57	5.72	<0.01	75	1.99	2173	<1	121	642	19	3.51	<5	<5	<10	201	5826	10	174	15	10	122
133645	1304220	<0.005	<1	7.15	9	352	<2	15	2.44	<4	15	54	23	3.28	<0.01	22	1.32	658	<1	30	515	9	1.72	<5	<5	<10	289	3150	4	114	19	14	55
133646	1304221	0.051	<1	7.60	3	45	2	3	8.00	<4	26	124	26	4.40	0.26	31	3.00	2538	<1	92	1017	10	1.33	6	<5	<10	198	4440	27	130	17	17	77
133647	1304222	0.007	<1	6.82	4	199	2	17	5.87	<4	40	157	50	4.43	<0.01	65	1.59	1130	<1	116	944	13	2.15	<5	<5	<10	226	6560	4	163	<10	12	101
133648	1304223	0.023	<1	7.49	8	214	2	17	5.10	<4	40	165	47	4.81	<0.01	64	1.69	1340	<1	121	983	15	2.40	7	<5	<10	226	6523	8	167	<10	13	113
133649D	1304223	0.027	<1	7.13	<2	195	2	16	5.18	<4	42	169	48	5.02	<0.01	54	1.88	1381	<1	128	1071	12	1.55	<5	<5	<10	220	6664	3	173	<10	14	115
133650	1304224	0.023	<1	>10.00	5	246	2	15	5.08	<4	37	153	40	3.82	0.36	43	2.07	1392	<1	107	1088	12	1.68	6	<5	<10	207	6428	9	158	<10	18	126
133651	1304225	0.073	1	>10.00	4	248	2	14	4.42	<4	41	147	52	4.91	<0.01	63	1.89	1546	<1	134	942	15	2.84	5	<5	<10	169	5989	10	153	<10	16	141
133652	1304226	0.045	<1	6.91	10	195	2	21	6.62	<4	37	127	63	5.45	<0.01	41	2.86	2024	<1	109	959	13	1.65	<5	<5	<10	171	5389	9	144	<10	17	148
133653	1304227	0.060	<1	8.31	13	187	2	6	6.09	<4	36	133	66	4.83	<0.01	39	2.45	1501	<1	98	962	13	2.10	<5	<5	<10	199	5415	2	140	10	15	118
133654	1304228	0.261	1	8.58	<2	147	2	16	3.22	<4	43	190	110	8.25	0.09	61	1.97	1280	<1	160	884	20	4.16	5	<5	<10	158	3923	3	125	<10	16	216
133655	1304229	0.118	1	9.94	5	217	2	9	5.15	<4	40	172	78	8.75	0.09	68	2.04	1569	<1	146	1016	22	3.84	<5	<5	<10	198	5590	4	163	<10	20	389
133656	1304230	0.247	1	3.92	401	>5000	<2	11	1.02	<4	5	20	29	2.85	0.26	12	0.40	<100	4	14	<100	22	1.79	19	<5	<10	157	1009	<2	18	43	10	27
133657	1304231	0.018	1	6.55	10	274	2	2	3.83	<4	23	91	29	6.98	<0.01	81	1.34	1857	<1	78	516	18	2.75	<5	<5	<10	194	3731	<2	92	<10	9	177
133658	1304232	0.006	<1	8.66	16	375	<2	15	2.22	<4	5	28	6	1.55	<0.01	59	0.84	391	<1	32	300	10	2.10	5	<5	<10	189	1526	6	30	<10	6	39
133659	1304233	<0.005	<1	9.24	4	378	<2	9	2.43	<4	4	38	6	1.66	<0.01	55	0.89	468	<1	54	301	14	2.05	<5	<5	<10	243	1629	2	33	<10	6	34
133660R	1304233	<0.005	<1	>10.00	2	356	2	7	2.39	<4	5	31	6	1.58	0.15	53	1.01	429	<1	43	358	12	2.10	7	<5	<10	242	1617	10	31	<10	9	28
133661	1304234	<0.005	<1	6.83	11	276	<2	15	1.68	<4	5	33	19	1.43	0.03	31	0.58	244	<1	55	332	17	0.99	<5	<5	<10	209	1533	<2	28	<10	6	108
133662	1304235	<0.005	<1	8.24	7	461	2	<1	1.82	<4	4	33	9	1.42	0.17	41	0.59	225	<1	48	306	14	1.42	<5	<5	<10	293	1659	<2	30	<10	6	70

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By:  Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 15, 2012

Certificate of Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
133663	1304236	<0.005	<1	9.31	3	481	<2	1	1.81	<4	4	27	6	1.40	0.13	43	0.64	221	<1	37	325	12	1.36	<5	<5	<10	293	1728	<2	30	<10	6	52
133664	1304237	<0.005	<1	7.96	4	339	<2	13	1.42	<4	3	40	4	1.18	0.20	32	0.57	160	<1	48	254	9	1.30	5	<5	<10	260	1359	<2	25	<10	6	35
133665	1304238	<0.005	<1	8.52	9	335	2	16	2.03	<4	4	46	10	1.60	0.18	32	0.61	326	<1	75	340	9	1.11	<5	<5	<10	321	1678	4	30	<10	7	42
133666	1304239	<0.005	1	9.32	3	235	2	5	2.68	<4	11	54	13	3.20	0.20	54	0.92	955	2	75	307	12	2.22	<5	<5	<10	283	2385	<2	33	<10	17	64
133667	1304240	<0.005	<1	8.49	6	346	2	12	2.38	<4	15	51	20	3.25	<0.01	16	1.49	645	<1	28	560	12	1.42	<5	<5	<10	288	3001	2	111	19	18	56
133668	1304241	0.007	<1	>10.00	8	193	2	10	4.60	<4	43	43	17	4.43	0.15	49	1.36	1312	<1	84	1564	9	1.81	<5	<5	<10	398	8688	6	187	<10	27	85
133669	1304242	0.009	<1	>10.00	3	204	2	8	4.99	<4	37	32	21	4.42	0.23	54	1.52	1490	<1	64	1455	13	1.98	<5	<5	<10	376	8585	10	177	<10	23	80
133670	1304243	0.015	1	>10.00	<2	208	2	8	4.19	<4	31	26	33	5.56	0.10	57	1.66	1461	<1	46	1379	9	2.38	<5	<5	<10	267	8793	6	184	<10	19	98
133671D	1304243	0.008	<1	>10.00	4	180	<2	13	4.16	<4	29	22	33	5.54	0.05	44	1.90	1404	<1	47	1448	10	1.45	<5	<5	<10	259	7903	12	182	<10	23	122
133672	1304244	<0.005	<1	7.22	7	238	2	12	4.33	<4	30	24	37	5.84	0.07	46	1.53	1318	<1	52	1264	11	1.64	<5	<5	<10	250	8041	<2	177	<10	16	99
133673	1304245	0.011	<1	6.78	<2	196	<2	11	3.95	<4	35	24	28	5.02	0.24	41	1.84	1134	<1	66	1378	7	0.86	<5	<5	<10	229	7912	12	180	<10	20	95
133674	1304246	0.008	<1	7.95	8	175	2	17	4.33	<4	33	32	36	5.65	0.09	47	1.35	1384	<1	65	1336	9	1.76	6	<5	<10	208	7965	<2	185	<10	17	99
133675	1304247	0.013	<1	8.04	3	260	2	7	4.76	<4	34	23	35	5.86	0.19	62	1.37	1361	<1	43	1278	7	1.86	<5	<5	<10	215	8972	<2	181	<10	16	138
133676	1304248	0.010	<1	6.83	7	255	2	16	4.36	<4	36	28	33	5.62	0.01	75	1.34	1461	<1	53	1205	12	1.90	<5	<5	<10	230	9664	12	188	<10	14	119
133677	1304249	0.012	2	9.20	359	1462	2	19	2.47	<4	11	108	73	3.36	0.09	26	1.36	451	6	47	749	28	2.57	33	<5	<10	207	2102	21	120	<10	18	197
133678	1304250	4.665	1	>10.00	6	225	2	19	5.93	<4	37	41	98	6.44	0.16	69	2.68	1651	1	67	967	15	3.49	<5	<5	<10	218	6876	12	137	14	19	596
133679	1304251	0.038	1	>10.00	3	147	2	<1	6.15	<4	49	227	82	8.14	0.05	81	2.37	2688	<1	171	919	19	3.12	6	<5	<10	203	6554	13	168	11	18	434
133680	1304252	0.036	<1	>10.00	5	132	3	7	6.68	<4	49	251	51	7.60	0.04	67	1.85	2461	<1	177	1037	16	2.25	6	<5	<10	207	7066	7	188	12	17	240
133681	1304253	0.043	<1	9.96	7	120	3	8	6.44	<4	48	245	49	7.39	0.11	62	1.84	2395	<1	177	1027	16	1.88	<5	<5	<10	198	6834	10	183	12	18	232
133682D	1304253	0.040	<1	9.50	4	229	2	18	4.28	<4	43	245	78	7.75	0.06	86	1.92	1702	<1	169	842	15	2.41	<5	<5	<10	167	5672	7	162	<10	17	285

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 15, 2012


Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm	
133683	1304254	0.086	<1	7.52	<2	349	4	6	1.91	<4	5	41	14	1.78	0.02	55	0.88	540	<1	69	473	10	1.92	<5	<5	<10	175	1678	8	35	<10	5	499	
133684	1304255	0.020	<1	8.32	5	303	4	16	1.80	<4	4	31	14	1.71	<0.01	55	1.01	612	<1	52	541	11	1.57	5	5	<10	162	1576	7	32	<10	6	269	
133685	1304256	0.023	<1	8.82	9	352	5	8	2.15	<4	5	37	21	1.77	<0.01	68	0.94	610	<1	71	573	7	1.66	<5	<5	<10	174	1498	2	32	<10	7	306	
133686	1304257	0.019	<1	7.15	2	235	2	11	6.16	<4	47	315	75	6.84	0.17	81	1.87	2000	<1	184	834	11	2.46	<5	<5	<10	199	7635	7	177	<10	15	251	
133687	1304258	0.019	<1	7.19	6	187	2	3	5.73	<4	52	319	57	6.38	0.18	65	1.51	1864	<1	167	888	11	2.37	<5	<5	<10	222	7813	8	178	<10	14	144	
133688	1304259	0.017	<1	8.30	5	184	2	7	6.58	<4	59	382	66	7.19	<0.01	65	1.67	2068	<1	199	1024	9	2.17	5	<5	<10	258	9148	2	209	<10	15	113	
133689	1304260	0.007	<1	8.18	8	358	<2	18	2.45	<4	15	53	21	3.39	0.06	15	1.52	674	<1	30	584	10	1.26	6	<5	<10	295	3108	11	117	21	18	51	
133690	1304261	0.015	<1	8.95	2	133	<2	20	6.53	<4	55	325	62	6.84	0.09	45	1.87	2048	<1	176	1072	8	1.78	<5	<5	<10	244	8486	11	194	<10	19	101	
133691	1304262	0.015	<1	>10.00	7	142	2	8	6.83	<4	56	345	63	7.18	0.08	57	1.94	1981	<1	202	1026	9	2.14	7	<5	<10	269	8037	7	195	<10	21	112	
133692	1304263	0.007	<1	>10.00	6	55	2	12	6.90	<4	55	334	61	7.61	0.07	46	1.85	2182	<1	182	1010	8	2.18	5	<5	<10	284	8213	11	199	<10	19	125	
133693D	1304263	0.014	<1	8.88	4	17	<2	20	6.69	<4	53	323	59	7.46	0.09	32	2.05	2080	<1	178	1034	7	1.30	5	<5	<10	264	7118	12	196	<10	22	127	
133694	1304264	0.012	<1	9.20	4	29	<2	8	5.83	<4	52	272	59	6.04	0.04	33	1.71	1915	<1	157	1076	9	1.53	<5	<5	<10	272	7454	7	188	<10	20	91	
133695	1304265	0.022	<1	8.46	3	52	<2	2	5.31	<4	54	286	56	5.08	0.04	32	1.48	1832	<1	163	1015	8	1.36	<5	<5	<10	305	6992	2	184	<10	19	143	
133696	1304266	0.012	<1	>10.00	<2	84	2	17	6.52	<4	57	308	51	8.04	0.28	35	1.96	2566	<1	180	1011	11	1.71	5	<5	<10	341	8037	11	190	<10	22	205	
133697	1304267	0.015	<1	9.51	5	453	<2	15	2.83	<4	18	78	15	2.68	0.09	43	1.27	817	<1	77	746	12	1.77	<5	<5	<10	294	3751	13	70	<10	11	133	
133698	1304268	0.013	<1	8.57	6	643	2	8	2.68	<4	14	36	19	2.81	0.15	52	0.95	548	<1	53	654	17	1.80	<5	<5	<10	300	3364	<2	63	<10	8	76	
133699	1304269	0.026	<1	9.26	7	218	<2	25	4.72	<4	36	26	32	5.16	0.13	64	1.75	1521	<1	60	1354	9	1.53	<5	<5	<10	370	9922	6	187	<10	19	114	
133700	1304270																																	
133701	1304271	0.027	<1	>10.00	6	227	<2	18	4.86	<4	34	17	31	4.47	0.14	66	1.50	1334	<1	37	1402	11	1.76	<5	<5	<10	385	9967	13	194	<10	20	83	
133702	1304272	0.020	<1	>10.00	4	412	2	14	3.51	<4	24	18	32	3.36	0.13	62	1.56	968	<1	38	1119	9	1.72	<5	<5	<10	271	6483	11	129	<10	18	88	

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 15, 2012

Certificate of Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm		
133703	1304273	0.024	<1	>10.00	8	678	<2	13	2.53	<4	8	21	6	2.00	0.01	49	0.91	375	<1	26	599	11	2.32	<5	<5	<10	252	2543	9	48	<10	9	57		
133704D	1304273	0.020	<1	>10.00	9	690	2	7	2.53	<4	8	26	7	1.99	0.04	56	0.92	372	<1	25	583	14	2.71	5	<5	<10	257	2604	8	49	<10	9	62		
133705	1304274	0.014	<1	8.95	4	236	<2	12	4.99	<4	28	17	43	4.63	0.08	46	1.66	1106	<1	40	1242	8	1.41	<5	<5	<10	290	7210	2	163	<10	20	80		
133706	1304275	0.018	<1	8.60	7	198	<2	14	4.81	<4	31	17	37	5.33	0.11	47	1.79	1389	<1	39	1179	9	1.70	<5	<5	<10	276	8214	8	173	<10	17	133		
133707	1304276	0.020	<1	8.63	8	174	<2	6	4.53	<4	30	17	33	5.18	0.12	44	1.81	1282	<1	42	1190	9	1.53	<5	<5	<10	267	7806	13	172	<10	18	120		
133708	1304277	0.016	<1	9.46	6	115	2	11	4.32	<4	30	18	30	4.80	0.15	33	1.84	1252	<1	42	1377	9	1.27	5	<5	<10	237	7223	4	178	<10	22	87		
133709	1304278	0.028	<1	9.10	<2	205	2	8	5.49	<4	52	249	83	7.49	0.06	46	2.06	2144	<1	166	989	14	1.91	<5	<5	<10	218	6770	3	175	<10	20	225		
133710	1304279	0.016	<1	8.54	5	123	2	22	4.05	<4	29	22	27	5.07	<0.01	43	1.43	1570	<1	46	1205	10	1.49	7	<5	<10	269	7168	<2	149	<10	18	158		
133711	1304280	<0.005	<1	5.92	5	335	2	3	2.29	<4	14	51	21	3.21	0.10	19	1.24	649	<1	27	515	12	1.50	<5	<5	<10	279	3051	4	112	19	12	56		
133712	1304281	0.019	<1	6.68	<2	172	2	2	4.76	<4	30	25	60	6.91	0.05	48	1.41	1903	<1	44	1041	9	2.18	<5	<5	<10	266	7597	3	144	<10	14	180		
133713	1304282	0.008	<1	8.07	2	213	2	14	1.15	<4	15	28	48	4.31	<0.01	43	1.08	717	<1	39	337	9	1.58	<5	<5	<10	234	2343	<2	28	<10	15	335		
133714	1304283	<0.005	<1	9.38	4	155	2	18	4.17	<4	24	28	11	4.74	0.16	34	1.48	1121	<1	49	1151	9	1.41	<5	<5	<10	336	6153	13	131	<10	20	122		
133715D	1304283	0.007	<1	>10.00	2	178	2	8	4.20	<4	25	26	10	4.70	0.14	43	1.37	1162	<1	40	1101	10	1.91	<5	<5	<10	340	7040	8	131	<10	18	127		
133716	1304284	0.012	<1	9.38	5	230	2	9	4.63	<4	28	17	23	5.26	0.19	43	1.59	1071	<1	33	1200	8	1.53	<5	<5	<10	335	7426	4	169	<10	19	92		
133717	1304285	0.015	<1	8.42	9	193	<2	6	5.02	<4	32	21	30	5.83	0.17	41	1.52	1067	<1	42	1226	9	1.42	5	<5	<10	315	7126	<2	169	<10	18	92		
133718	1304286	0.032	<1	7.68	7	184	2	12	5.44	<4	34	15	45	6.25	0.11	49	2.08	1271	<1	37	1208	11	1.90	6	<5	<10	297	6758	10	167	<10	17	96		
133719	1304287	0.020	<1	6.05	<2	182	2	7	3.86	<4	37	19	39	6.18	0.04	47	1.43	968	<1	40	1178	10	2.09	6	<5	<10	259	7805	3	171	<10	12	101		
133720	1304288	0.014	<1	7.76	4	187	2	17	4.41	<4	32	13	31	6.24	0.11	33	1.92	894	<1	37	1335	9	1.08	7	<5	<10	292	5080	<2	171	<10	21	98		
133721	1304289	0.028	<1	9.51	9	262	<2	<1	4.40	<4	36	16	28	6.49	0.21	43	1.93	975	<1	40	1287	9	1.54	7	<5	<10	341	7108	8	173	<10	20	96		
133722	1304290																																		NS

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 15, 2012


Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
133723	1304291	0.006	<1	8.78	6	142	2	11	4.37	<4	33	13	45	6.29	0.03	32	1.94	908	<1	36	1313	7	1.36	<5	<5	<10	309	5568	5	170	<10	21	107
133724	1304292	0.012	<1	8.33	3	127	<2	5	4.07	<4	34	21	28	6.00	0.11	31	1.71	953	<1	43	1194	11	1.48	<5	<5	<10	276	7294	3	159	<10	18	92
133725	1304293	0.015	<1	5.80	6	111	<2	7	4.40	<4	29	15	28	6.14	0.11	19	1.86	1002	<1	43	1386	8	0.80	7	<5	<10	255	4213	<2	170	<10	21	104
133726R	1304293	0.014	<1	7.18	<2	121	2	<1	4.56	<4	33	16	27	6.28	0.14	21	1.87	1085	<1	45	1337	8	0.92	<5	<5	<10	290	6592	4	174	<10	21	99
133727	1304294	0.145	<1	7.81	3	128	2	11	4.54	<4	35	11	29	6.48	0.20	29	1.95	1027	<1	35	1342	11	1.05	<5	<5	<10	285	6708	10	177	<10	21	102
133728	1304295	0.026	<1	8.71	3	249	2	14	5.05	<4	37	17	33	6.71	0.24	45	2.26	1398	<1	45	1406	9	1.75	<5	<5	<10	259	8213	4	176	<10	21	116
133729	1304296	0.022	<1	9.16	5	241	2	20	5.20	<4	38	22	32	6.92	0.27	46	2.34	1459	<1	53	1421	10	1.87	<5	<5	<10	269	8840	11	183	<10	22	115
133730	1304297	0.032	<1	8.19	3	129	2	16	4.88	<4	53	215	65	7.42	0.14	45	2.56	1712	<1	148	1214	11	1.87	<5	<5	<10	235	6156	6	181	<10	23	243
133731	1304298	0.068	<1	9.13	6	169	2	10	5.16	<4	54	276	90	8.07	0.22	45	2.07	1809	<1	182	1091	14	2.37	6	<5	<10	242	6402	5	186	<10	21	344
133732	1304299	0.163	<1	6.43	3	38	2	14	6.20	<4	38	129	122	11.33	0.26	38	1.87	3031	<1	105	623	17	3.25	<5	<5	<10	177	3608	7	118	<10	16	594
133733	1304300	0.008	<1	6.05	10	340	<2	<1	2.26	<4	15	49	22	3.37	0.23	8	1.44	679	<1	29	569	9	0.99	5	<5	<10	282	2938	<2	114	18	17	54
133734	1304301	0.081	<1	6.56	7	131	2	5	5.56	<4	41	194	69	5.53	0.18	28	1.53	1550	<1	127	852	9	1.51	<5	<5	<10	236	5036	6	145	<10	19	398
133735	1304302	0.050	<1	5.86	4	228	<2	12	5.95	<4	54	297	47	5.18	0.09	40	1.61	1622	<1	159	1122	8	1.22	<5	<5	<10	228	9087	7	198	<10	18	136
133736	1304303	0.008	<1	7.02	2	175	2	11	6.00	<4	54	305	98	7.20	0.12	41	1.86	1756	<1	173	1223	9	1.55	5	<5	<10	222	8632	6	206	<10	20	133
133737D	1304303	0.010	<1	8.09	6	176	2	3	6.36	<4	57	313	105	7.53	0.21	37	2.15	1790	<1	179	1326	8	1.25	<5	<5	<10	228	8235	2	209	<10	26	139
133738	1304304	0.049	<1	8.39	4	122	<2	6	6.21	<4	54	318	60	6.97	0.15	32	1.94	1726	<1	191	1263	8	1.16	<5	<5	<10	285	8686	11	204	<10	25	120
133739	1304305	0.024	<1	6.57	11	101	<2	18	6.38	<4	58	310	73	7.60	0.27	32	1.80	1827	<1	173	1118	11	1.25	5	<5	<10	274	10664	6	213	<10	20	144
133740	1304306	0.083	<1	5.80	5	234	<2	9	5.98	<4	58	295	52	5.36	0.02	43	1.72	1383	<1	188	1055	11	0.96	<5	<5	<10	249	8052	2	191	<10	15	174
133741	1304307	0.013	<1	6.58	4	269	<2	7	6.75	<4	59	301	55	5.32	0.16	47	1.58	1642	<1	192	1042	10	1.12	<5	<5	<10	268	8086	4	195	<10	16	221
133742	1304308	0.017	<1	8.83	<2	296	2	13	6.11	<4	65	301	78	5.59	0.28	45	1.74	1789	<1	219	1039	6	1.34	<5	<5	<10	272	6727	6	187	<10	20	444

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By:  Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 15, 2012

Certificate of Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
133743	1304309	0.018	<1	9.21	2	228	2	7	5.19	<4	34	126	66	6.45	0.17	41	1.94	1733	<1	83	674	11	2.36	<5	<5	<10	288	4612	12	127	<10	17	534
133744	1304310	4.967	1	6.46	364	1391	<2	10	2.26	<4	11	109	76	3.35	0.15	17	1.27	453	6	47	739	29	1.95	37	<5	<10	193	1979	20	119	<10	16	204
133745	1304311	0.015	<1	9.22	8	185	<2	3	4.88	<4	30	59	36	5.30	0.15	30	1.52	1263	<1	55	1012	9	1.10	<5	<5	<10	301	5668	5	159	<10	17	92
133746	1304312	0.019	<1	6.30	6	167	<2	13	4.99	<4	28	30	36	5.23	0.08	35	1.26	1863	<1	63	1305	9	1.00	<5	<5	<10	267	7405	10	160	<10	18	84
133747	1304313	0.021	<1	6.67	5	107	<2	5	4.98	<4	33	21	27	4.79	0.07	29	1.50	1531	<1	55	1262	6	1.04	5	<5	<10	240	7549	8	172	<10	17	95
133748D	1304313	0.019	<1	7.32	3	109	<2	4	5.04	<4	35	20	27	4.90	0.11	30	1.58	1594	<1	50	1275	6	1.00	5	<5	<10	242	8393	10	175	<10	18	97
133749	1304314	0.017	<1	8.32	4	99	<2	17	5.08	<4	34	23	27	6.29	0.27	28	1.70	1407	<1	57	1354	8	1.09	<5	<5	<10	223	7055	<2	184	<10	21	112
133750	1304315	0.024	<1	8.39	3	190	2	6	5.13	<4	38	18	29	4.80	0.10	48	1.73	1455	<1	47	1419	6	1.02	<5	<5	<10	199	9439	2	182	<10	22	105
133751	1304316	0.025	<1	7.17	8	188	2	16	4.95	<4	38	32	33	4.90	0.28	49	1.58	1465	<1	76	1459	7	0.86	<5	<5	<10	199	9733	3	182	<10	20	111
133752	1304317	0.084	<1	6.74	7	226	<2	<1	3.87	<4	32	48	25	3.37	0.15	36	0.95	1154	2	92	797	8	1.16	<5	<5	<10	176	5405	9	96	<10	21	59
133753	1304318	0.036	<1	6.85	2	136	<2	12	5.00	<4	29	142	58	6.91	0.02	47	1.84	1866	<1	117	580	10	2.37	<5	<5	<10	160	4692	16	98	<10	20	191
133754	1304319	0.111	1	7.36	3	<1	2	11	4.76	4	57	162	118	15.87	0.14	51	2.39	3282	<1	127	685	21	9.05	6	<5	<10	307	4357	9	136	<10	17	197
133755	1304320	0.009	<1	7.31	12	339	<2	7	2.31	<4	15	50	21	3.33	0.11	12	1.47	667	<1	28	562	8	1.23	<5	<5	<10	284	3024	8	113	18	17	57
133756	1304321	0.144	1	8.79	4	<1	2	13	4.24	<4	31	161	83	13.97	0.14	54	2.26	3677	<1	124	763	16	5.90	6	<5	<10	356	4046	2	140	<10	18	188
133757	1304322	0.096	1	6.61	<2	30	2	18	3.57	<4	33	113	113	15.87	0.20	70	2.12	3274	<1	122	746	20	6.96	7	<5	<10	247	3087	10	122	<10	14	182
133758	1304323	0.058	<1	7.01	<2	88	2	9	3.52	<4	38	114	58	9.69	0.09	66	2.01	1807	<1	110	854	16	5.02	5	<5	<10	250	3448	9	126	<10	14	115
133759D	1304323	0.054	<1	7.44	2	85	2	6	3.49	<4	37	111	56	9.52	0.25	64	2.05	1775	<1	108	849	13	4.87	6	<5	<10	247	3550	2	125	<10	15	112
133760	1304324	0.020	3	8.55	8	247	2	11	4.49	<4	46	104	30	6.49	0.20	83	2.17	1358	<1	94	825	7	3.17	<5	<5	<10	171	4335	19	131	<10	15	111
133761	1304325	0.030	<1	9.04	6	207	<2	23	3.67	<4	40	101	146	7.86	0.37	78	2.23	1848	<1	143	810	11	3.08	5	<5	<10	207	4679	13	124	<10	17	386
133762	1304326	0.052	<1	5.54	<2	19	2	17	3.67	6	50	105	180	12.48	0.13	36	1.51	2726	2	206	855	19	2.90	6	<5	<10	184	3712	7	92	12	13	917

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 15, 2012


Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
133763	1304327	0.016	<1	7.50	4	284	<2	13	4.97	<4	34	147	45	6.14	0.34	40	1.01	1839	<1	114	1026	21	1.36	<5	<5	<10	224	6091	4	146	<10	14	221
133764	1304328	0.011	<1	5.48	6	169	<2	3	2.23	<4	4	24	9	1.39	0.24	16	0.48	386	<1	40	287	18	1.03	<5	<5	<10	239	1504	<2	29	<10	5	45
133765	1304329	0.011	<1	5.42	2	159	2	2	1.93	<4	2	60	7	1.19	0.08	18	0.53	280	3	91	217	16	1.11	5	<5	<10	252	1069	<2	30	<10	6	30
133766	1304330	1.824	<1	6.48	10	370	<2	<1	2.22	<4	16	51	31	3.83	0.02	11	1.51	713	<1	32	609	13	0.97	<5	<5	<10	279	3084	2	124	23	17	68
133767	1304331	<0.005	<1	3.39	<2	13	<2	10	0.66	<4	<1	66	4	0.88	0.24	11	0.54	198	2	80	100	10	1.38	<5	<5	<10	117	565	<2	15	<10	5	26
133768	1304332	<0.005	<1	8.36	9	423	2	7	1.50	<4	3	33	6	1.32	0.39	28	0.62	231	<1	47	253	12	1.40	<5	<5	<10	458	1522	<2	39	<10	7	38
133769	1304333	0.011	<1	7.29	9	354	<2	14	1.32	<4	4	25	9	1.37	0.43	21	0.55	240	<1	40	336	10	1.23	<5	<5	<10	331	1477	<2	28	<10	6	35
133770D	1304333	<0.005	<1	7.22	4	353	<2	11	1.33	<4	3	27	9	1.41	0.29	20	0.54	243	<1	45	339	11	1.24	<5	<5	<10	335	1485	<2	28	<10	6	31
133771	1304334	0.008	<1	5.11	6	231	<2	<1	1.71	<4	4	25	6	1.37	0.40	17	0.50	236	<1	35	335	9	1.63	5	<5	<10	332	1481	<2	27	<10	5	40
133772	1304335	0.008	<1	7.31	6	334	<2	4	1.52	<4	4	25	2	1.33	0.06	25	0.55	212	<1	32	343	11	1.29	<5	<5	<10	384	1526	<2	27	<10	6	42
133773	1304336	0.008	<1	7.54	5	377	<2	7	1.41	<4	4	32	2	1.36	0.25	25	0.56	206	<1	44	347	8	1.20	<5	<5	<10	358	1501	<2	27	<10	6	41
133774	1304337	0.010	<1	7.98	5	417	<2	3	3.56	<4	26	113	11	3.14	0.24	41	1.53	645	<1	93	843	5	1.54	<5	<5	<10	515	4478	3	107	<10	12	92
133775	1304338	0.011	<1	8.08	7	107	<2	7	4.86	<4	40	152	34	4.23	0.27	37	2.09	886	<1	126	1046	7	1.45	5	<5	<10	338	5395	11	147	<10	17	110
133776	1304339	0.047	<1	8.22	8	83	<2	14	4.15	<4	46	178	137	4.97	0.09	67	2.56	827	<1	173	1025	7	1.43	<5	<5	<10	395	5926	13	147	<10	15	120
133777	1304340	0.005	<1	6.80	12	349	<2	5	2.33	<4	15	51	22	3.36	<0.01	11	1.48	676	<1	29	582	11	1.06	<5	<5	<10	289	3169	9	116	20	17	53
133778	1304341	0.035	<1	9.08	8	127	<2	12	4.84	<4	37	154	95	4.54	0.25	33	2.28	896	<1	130	942	9	1.12	5	<5	<10	399	5016	9	149	<10	16	101
133779	1304342	0.007	<1	9.62	5	235	<2	9	4.14	<4	30	163	47	3.50	0.21	45	1.88	744	<1	124	694	7	1.10	<5	<5	<10	514	4530	21	118	<10	13	108
133780	1304343	0.010	<1	9.36	3	168	<2	11	4.65	<4	34	151	37	3.69	0.23	35	1.87	808	<1	113	912	7	1.38	<5	<5	<10	345	5446	21	135	<10	15	114
133781D	1304343	0.017	<1	9.19	2	163	<2	11	4.52	<4	33	146	36	3.61	0.14	36	1.84	786	<1	109	897	9	1.46	6	<5	<10	331	5281	20	133	<10	15	88
133782	1304344	0.017	<1	8.37	<2	225	<2	13	5.14	<4	43	171	45	4.22	0.10	38	2.02	820	<1	135	1084	7	1.14	5	<5	<10	271	6597	13	163	<10	17	110

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 15, 2012

Certificate of Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
133783	1304345	0.018	<1	7.50	4	263	2	1	3.16	<4	18	84	19	2.44	<0.01	34	1.22	471	<1	74	661	7	1.30	5	<5	<10	289	3809	3	91	<10	10	49
133784	1304346	0.009	<1	7.68	5	349	<2	4	2.89	<4	17	64	35	2.46	<0.01	34	1.19	452	<1	61	559	9	1.41	7	<5	<10	297	3275	2	70	<10	9	71
133785	1304347	0.009	<1	8.25	5	231	<2	6	2.81	<4	11	48	28	2.08	0.19	24	0.90	421	<1	48	473	9	1.40	<5	<5	<10	221	2610	7	54	<10	9	66
133786	1304348	0.007	<1	8.19	2	112	<2	7	4.74	<4	36	149	88	4.17	0.04	31	1.88	844	<1	114	1044	6	1.08	<5	<5	<10	239	6272	11	148	<10	16	97
133787	1304349	0.010	<1	9.42	10	166	<2	14	4.89	<4	42	167	44	4.47	0.05	35	2.11	771	<1	129	1197	5	1.16	<5	<5	<10	243	6853	11	167	<10	18	95
133788	1304350	0.257	1	1.99	405	>5000	<2	12	0.86	<4	5	18	30	2.84	<0.01	7	0.32	<100	4	13	<100	25	1.59	21	<5	<10	135	1095	4	18	48	9	19
133789	1304351	0.011	<1	9.37	6	305	<2	21	5.32	<4	38	164	40	4.62	0.21	41	2.14	940	<1	122	1099	8	1.25	5	<5	<10	229	6297	11	154	<10	18	96
133790	1304352	0.010	<1	9.36	5	356	<2	10	6.09	<4	35	143	25	4.39	0.02	41	2.70	1595	<1	91	1004	8	1.06	<5	<5	<10	272	6059	6	147	<10	17	93
133791	1304353	<0.005	<1	8.99	4	340	<2	11	4.44	<4	26	111	30	3.22	0.09	41	1.55	593	<1	85	788	11	1.50	5	<5	<10	261	4691	4	110	<10	12	58
133792R	1304353	<0.005	<1	8.92	5	332	<2	9	4.25	<4	25	117	29	3.19	0.16	38	1.56	574	<1	103	766	10	1.27	<5	<5	<10	250	4507	17	106	<10	13	56
133793	1304354	<0.005	<1	7.42	6	321	<2	9	3.55	<4	18	77	23	2.64	0.22	33	1.40	597	<1	73	548	9	1.26	5	<5	<10	251	3331	5	80	<10	9	77
133794	1304355	0.011	<1	8.50	8	249	<2	9	5.20	<4	37	147	41	4.34	0.11	36	1.99	893	<1	121	904	8	1.25	<5	<5	<10	268	5534	9	138	<10	17	87
133795	1304356	0.010	<1	8.42	7	247	<2	9	5.26	<4	37	147	40	4.30	0.08	35	1.98	878	<1	119	902	7	1.14	<5	<5	<10	273	5620	10	140	<10	16	84
133796	1304357	0.018	<1	8.16	5	371	2	7	4.95	<4	52	239	68	6.77	0.03	53	2.29	1221	<1	158	1224	10	1.95	<5	<5	<10	227	9373	13	194	<10	23	148
133797	1304358	0.009	<1	6.43	3	66	2	28	5.17	<4	50	72	111	10.19	0.03	43	2.83	1347	<1	70	910	12	1.62	6	<5	<10	211	6194	<2	341	<10	40	145
133798	1304359	0.016	<1	6.58	<2	379	2	21	6.79	<4	43	58	76	8.97	0.05	36	2.37	1443	<1	55	841	10	1.53	<5	<5	<10	407	7022	2	291	10	40	130
133799	1304360	<0.005	<1	6.02	11	335	<2	<1	2.24	<4	15	48	21	3.32	0.02	8	1.43	658	<1	29	561	10	0.98	<5	<5	<10	280	2936	11	114	18	17	56
133800	1304361	0.009	<1	6.47	2	130	2	14	5.26	<4	45	71	90	8.48	0.10	37	2.19	1622	<1	71	780	8	1.32	<5	<5	<10	249	6816	<2	277	<10	37	125
133801	1304362	0.015	<1	8.06	<2	27	2	12	6.40	<4	52	64	84	10.46	0.24	39	2.96	1809	<1	69	957	11	1.54	<5	<5	<10	221	8224	12	365	<10	41	160
133802	1304363	0.014	<1	7.70	4	54	2	16	5.33	<4	54	83	85	8.35	0.50	41	2.26	1915	<1	84	785	8	1.50	<5	<5	<10	226	8912	9	329	<10	34	117

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 15, 2012


Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
133803D	1304363	0.011	<1	6.22	4	50	2	5	5.12	<4	54	80	83	8.11	0.44	40	2.08	1886	<1	79	753	10	1.53	<5	<5	<10	219	8915	4	322	<10	29	115
133804	1304364	0.010	<1	6.86	4	<1	2	17	6.12	<4	54	83	71	9.77	0.42	37	2.16	1888	<1	69	775	10	1.49	5	<5	<10	273	9090	2	335	<10	32	137
133805	1304365	0.009	<1	7.70	2	2	2	15	6.35	<4	57	83	101	10.28	0.42	35	2.37	1750	<1	71	827	11	1.26	<5	<5	<10	282	9485	14	342	<10	37	145
133806	1304366	0.010	<1	8.10	4	65	2	10	6.05	<4	53	86	100	9.57	0.16	37	2.42	1763	<1	75	807	9	1.34	<5	<5	<10	248	8039	<2	335	<10	38	133
133807	1304367	0.008	<1	7.15	2	17	<2	11	5.20	<4	49	79	77	9.50	0.05	41	2.61	1923	<1	66	794	13	1.01	<5	<5	<10	216	7137	2	321	<10	36	129
133808	1304368	0.013	<1	7.33	<2	7	2	19	6.54	<4	48	74	183	13.30	<0.01	44	2.85	2915	<1	69	624	15	2.20	<5	<5	<10	171	6680	5	308	<10	38	175
133809	1304369	0.012	<1	6.52	<2	109	2	10	6.25	<4	48	76	122	11.41	0.06	45	2.89	2360	<1	67	711	13	1.53	5	<5	<10	199	6519	<2	305	<10	37	163
133810	1304370	3.893	1	4.94	343	1357	2	9	2.05	<4	11	98	71	3.18	0.06	11	1.18	423	5	46	702	25	1.59	32	<5	<10	180	1787	4	115	11	15	197
133811	1304371	0.034	<1	6.81	7	60	2	10	5.87	<4	48	77	112	10.09	0.10	34	2.48	1919	<1	68	752	12	1.25	6	<5	<10	222	6422	4	313	<10	35	134
133812	1304372	0.012	<1	6.17	4	14	2	13	5.95	<4	49	77	78	9.36	0.16	27	2.44	1708	<1	64	727	11	0.84	5	<5	<10	229	6542	2	344	<10	37	127
133813	1304373	0.010	<1	6.90	3	31	2	11	5.66	<4	47	82	83	8.96	0.17	29	2.35	1589	<1	74	791	10	0.88	<5	<5	<10	240	6784	12	316	<10	36	117
133814D	1304373	0.009	<1	7.66	<2	34	<2	11	5.70	<4	49	83	86	8.98	0.45	32	2.32	1619	<1	79	789	8	1.13	5	<5	<10	243	7244	<2	315	<10	35	120
133815	1304374	0.010	<1	6.80	3	85	2	14	5.61	<4	53	83	85	9.71	0.35	50	2.43	1811	<1	69	786	11	1.41	<5	<5	<10	253	9204	8	330	<10	30	135
133816	1304375	0.012	<1	6.78	6	84	2	17	5.83	<4	53	80	104	9.33	0.33	32	2.06	1948	<1	65	807	13	1.14	<5	<5	<10	271	8967	<2	344	<10	33	130
133817	1304376	0.012	<1	6.57	6	74	2	8	5.80	<4	53	79	110	9.29	0.32	32	2.06	1961	<1	73	785	9	1.11	<5	<5	<10	269	9173	5	340	<10	32	128
133818	1304377	0.011	<1	9.15	4	73	2	24	5.83	<4	53	83	93	8.91	0.11	34	2.48	1720	<1	65	825	11	1.19	<5	<5	<10	260	8431	2	345	<10	39	123
133819	1304378	0.013	<1	7.69	4	76	2	22	6.13	<4	50	82	98	9.64	0.02	34	2.50	1815	<1	71	837	9	1.17	<5	<5	<10	266	6918	3	327	<10	37	136
133820	1304379	0.011	<1	7.74	<2	<1	<2	18	6.85	<4	47	73	97	10.93	0.11	37	2.58	2729	<1	68	692	10	1.30	<5	<5	<10	262	7047	17	299	<10	38	138
133821	1304380	0.007	<1	5.89	3	320	<2	13	2.14	<4	14	46	19	3.19	0.02	8	1.39	637	<1	26	542	9	0.81	<5	<5	<10	268	2846	13	109	17	16	53
133822	1304381	0.013	<1	5.72	3	46	2	7	4.92	<4	43	76	83	10.86	0.06	49	2.49	2326	<1	72	660	12	1.21	6	<5	<10	185	5316	<2	292	<10	35	165

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 15, 2012


Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
133823	1304382	0.012	<1	4.63	4	96	<2	13	4.22	<4	46	77	72	8.76	0.18	43	2.09	1761	<1	97	675	11	0.79	<5	<5	<10	213	4754	5	264	<10	29	144
133824	1304383	0.024	<1	6.87	4	317	2	8	3.64	<4	32	61	66	5.49	0.12	72	1.98	1201	<1	60	487	12	1.15	8	<5	<10	224	4411	5	170	<10	18	104
133825D	1304383	0.026	<1	7.70	5	322	2	7	3.75	<4	31	62	66	5.46	0.16	73	2.00	1210	<1	63	483	11	1.23	<5	<5	<10	233	4633	5	172	<10	18	103
133826	1304384	0.027	<1	6.38	6	281	<2	6	4.22	<4	31	56	56	5.01	0.33	62	1.55	1043	<1	62	513	13	1.28	<5	<5	<10	232	5082	8	172	<10	19	105

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Tuesday, May 29, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
133463	1185922	49	0.001	0.049
133464	1185923	58	0.002	0.058
133465	1185924	34	<0.001	0.034
133466	1185925	11	<0.001	0.011
133467	1185926	13	<0.001	0.013
133468	1185927	31	<0.001	0.031
133469	1185928	14	<0.001	0.014
133470	1185929	12	<0.001	0.012
133471	1185930	258	0.008	0.258
133472	1185931	21	<0.001	0.021
133473 Dup	1185931	20	<0.001	0.020
133474	1185932	18	<0.001	0.018
133475	1185933	20	<0.001	0.020
133476	1185934	20	<0.001	0.020
133477	1185935	15	<0.001	0.015
133478	1185936	13	<0.001	0.013
133479	1185937	20	<0.001	0.020
133480	1185938	37	0.001	0.037
133481	1185939	52	0.002	0.052
133482	1185940	6	<0.001	0.006
133483	1185941	78	0.002	0.078
133484 Dup	1185941	89	0.003	0.089
133485	1185942	113	0.003	0.113
133486	1185943	30	<0.001	0.030
133487	1185944	82	0.002	0.082
133488	1185945	37	0.001	0.037
133489	1185946	51	0.002	0.051
133490	1185947	35	0.001	0.035
133491	1185948	23	<0.001	0.023
133492	1185949	60	0.002	0.060

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, May 29, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
133493	1185950	4335	0.126	4.335
133494	1185951	22	<0.001	0.022
133495 Dup	1185951	37	0.001	0.037
133496	1185952	67	0.002	0.067
133497	1185953	35	0.001	0.035
133498	1185954	47	0.001	0.047
133499	1185955	21	<0.001	0.021
133500	1185956	26	<0.001	0.026
133501	1185957	46	0.001	0.046
133502	1185958	162	0.005	0.162
133503	1185959	44	0.001	0.044
133504	1185960	<5	<0.001	<0.005
133505	1185961	44	0.001	0.044
133506 Dup	1185961	104	0.003	0.104
133507	1185962	44	0.001	0.044
133508	1185963	82	0.002	0.082
133509	1185964	674	0.020	0.674
133510	1185965	3872	0.113	3.872
133511	1185966	55	0.002	0.055
133512	1185967	68	0.002	0.068
133513	1185968	49	0.001	0.049
133514	1185969	26	<0.001	0.026
133515	1185970	1175	0.034	1.175
133516	1185971	85	0.002	0.085
133517 Dup	1185971	109	0.003	0.109
133518	1185972	78	0.002	0.078
133519	1185973	341	0.010	0.341
133520	1185974	11	<0.001	0.011
133521	1185975	10	<0.001	0.010
133522	1185976	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, May 29, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
133523	1185977	<5	<0.001	<0.005
133524	1185978	<5	<0.001	<0.005
133525	1185979	<5	<0.001	<0.005
133526	1185980	<5	<0.001	<0.005
133527	1185981	10	<0.001	0.010
133528 Rep	1185981	6	<0.001	0.006
133529	1185982	9	<0.001	0.009
133530	1185983	170	0.005	0.170
133531	1185984	176	0.005	0.176
133532	1185985	72	0.002	0.072
133533	1185986	15	<0.001	0.015
133534	1185987	9	<0.001	0.009
133535	1185988	442	0.013	0.442
133536	1185989	147	0.004	0.147
133537	1185990	228	0.007	0.228
133538	1185991	59	0.002	0.059
133539 Dup	1185991	22	<0.001	0.022
133540	1185992	<5	<0.001	<0.005
133541	1185993	18	<0.001	0.018
133542	1185994	11	<0.001	0.011
133543	1185995	24	<0.001	0.024
133544	1185996	34	<0.001	0.034
133545	1185997	59	0.002	0.059
133546	1185998	78	0.002	0.078
133547	1185999	87	0.003	0.087
133548	1186000	<5	<0.001	<0.005
133549	1304001	48	0.001	0.048
133550 Dup	1304001	22	<0.001	0.022
133551	1304002	142	0.004	0.142
133552	1304003	177	0.005	0.177

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, May 29, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
133553	1304004	46	0.001	0.046
133554	1304005	37	0.001	0.037
133555	1304006	96	0.003	0.096
133556	1304007	178	0.005	0.178
133557	1304008	32	<0.001	0.032
133558	1304009	119	0.003	0.119
133559	1304010	4332	0.126	4.332
133560	1304011	62	0.002	0.062
133561 Dup	1304011	50	0.001	0.050
133562	1304012	32	<0.001	0.032
133563	1304013	27	<0.001	0.027
133564	1304014	25	<0.001	0.025
133565	1304015	16	<0.001	0.016
133566	1304016	12	<0.001	0.012
133567	1304017	233	0.007	0.233
133568	1304018	47	0.001	0.047
133569	1304019	50	0.001	0.050
133570	1304020	5	<0.001	0.005
133571	1304021	46	0.001	0.046
133572 Dup	1304021	43	0.001	0.043
133573	1304022	60	0.002	0.060
133574	1304023	114	0.003	0.114
133575	1304024	13	<0.001	0.013
133576	1304025	82	0.002	0.082
133577	1304026	7	<0.001	0.007
133578	1304027	49	0.001	0.049
133579	1304028	2422	0.071	2.422
133580	1304029	39	0.001	0.039
133581	1304030	1292	0.038	1.292
133582	1304031	29	<0.001	0.029

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, May 29, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
133583 Dup	1304031	62	0.002	0.062
133584	1304032	77	0.002	0.077
133585	1304033	21	<0.001	0.021
133586	1304034	17	<0.001	0.017
133587	1304035	14	<0.001	0.014
133588	1304036	14	<0.001	0.014
133589	1304037	17	<0.001	0.017
133590	1304038	85	0.002	0.085
133591	1304039	14	<0.001	0.014
133592	1304040	<5	<0.001	<0.005
133593	1304041	19	<0.001	0.019
133594 Rep	1304041	35	0.001	0.035
133595	1304042	21	<0.001	0.021
133596	1304043	16	<0.001	0.016
133597	1304044	25	<0.001	0.025
133598	1304045	23	<0.001	0.023
133599	1304046	348	0.010	0.348
133600	1304047	70	0.002	0.070
133601	1304048	14	<0.001	0.014
133602	1304049	23	<0.001	0.023
133603	1304050	222	0.006	0.222
133604	1304051	26	<0.001	0.026
133605 Dup	1304051	25	<0.001	0.025
133606	1304052	24	<0.001	0.024
133607	1304053	25	<0.001	0.025
133608	1304054	20	<0.001	0.020
133609	1304055	64	0.002	0.064
133610	1304056	70	0.002	0.070
133611	1304057	30	<0.001	0.030
133612	1304058	22	<0.001	0.022

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, May 29, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
133613	1304059	50	0.001	0.050
133614	1304060	<5	<0.001	<0.005
133615	1304061	54	0.002	0.054
133616 Dup	1304061	43	0.001	0.043
133617	1304062	63	0.002	0.063
133618	1304063	80	0.002	0.080
133619	1304064	27	<0.001	0.027
133620	1304065	23	<0.001	0.023
133621	1304066	173	0.005	0.173
133622	1304067	23	<0.001	0.023
133623	1304068	13	<0.001	0.013
133624	1304069	34	<0.001	0.034
133625	1304070	4775	0.139	4.775
133626	1304071	60	0.002	0.060
133627 Dup	1304071	50	0.001	0.050
133628	1304072	43	0.001	0.043
133629	1304073	10	<0.001	0.010
133630	1304074	17	<0.001	0.017
133631	1304075	21	<0.001	0.021
133632	1304076	15	<0.001	0.015
133633	1304209	37	0.001	0.037
133634	1304210	Insufficient Sample		
133635	1304211	43	0.001	0.043
133636	1304212	55	0.002	0.055
133637	1304213	9	<0.001	0.009
133638 Dup	1304213	39	0.001	0.039
133639	1304214	18	<0.001	0.018
133640	1304215	441	0.013	0.441
133641	1304216	137	0.004	0.137
133642	1304217	101	0.003	0.101

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, May 29, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
133643	1304218	4594	0.134	4.594
133644	1304219	107	0.003	0.107
133645	1304220	<5	<0.001	<0.005
133646	1304221	51	0.001	0.051
133647	1304222	7	<0.001	0.007
133648	1304223	23	<0.001	0.023
133649 Dup	1304223	27	<0.001	0.027
133650	1304224	23	<0.001	0.023
133651	1304225	73	0.002	0.073
133652	1304226	45	0.001	0.045
133653	1304227	60	0.002	0.060
133654	1304228	261	0.008	0.261
133655	1304229	118	0.003	0.118
133656	1304230	247	0.007	0.247
133657	1304231	18	<0.001	0.018
133658	1304232	6	<0.001	0.006
133659	1304233	<5	<0.001	<0.005
133660 Rep	1304233	<5	<0.001	<0.005
133661	1304234	<5	<0.001	<0.005
133662	1304235	<5	<0.001	<0.005
133663	1304236	<5	<0.001	<0.005
133664	1304237	<5	<0.001	<0.005
133665	1304238	<5	<0.001	<0.005
133666	1304239	<5	<0.001	<0.005
133667	1304240	<5	<0.001	<0.005
133668	1304241	7	<0.001	0.007
133669	1304242	9	<0.001	0.009
133670	1304243	15	<0.001	0.015
133671 Dup	1304243	8	<0.001	0.008
133672	1304244	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, May 29, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
133673	1304245	11	<0.001	0.011
133674	1304246	8	<0.001	0.008
133675	1304247	13	<0.001	0.013
133676	1304248	10	<0.001	0.010
133677	1304249	12	<0.001	0.012
133678	1304250	4665	0.136	4.665
133679	1304251	38	0.001	0.038
133680	1304252	36	0.001	0.036
133681	1304253	43	0.001	0.043
133682 Dup	1304253	40	0.001	0.040
133683	1304254	86	0.003	0.086
133684	1304255	20	<0.001	0.020
133685	1304256	23	<0.001	0.023
133686	1304257	19	<0.001	0.019
133687	1304258	19	<0.001	0.019
133688	1304259	17	<0.001	0.017
133689	1304260	7	<0.001	0.007
133690	1304261	15	<0.001	0.015
133691	1304262	15	<0.001	0.015
133692	1304263	7	<0.001	0.007
133693 Dup	1304263	14	<0.001	0.014
133694	1304264	12	<0.001	0.012
133695	1304265	22	<0.001	0.022
133696	1304266	12	<0.001	0.012
133697	1304267	15	<0.001	0.015
133698	1304268	13	<0.001	0.013
133699	1304269	26	<0.001	0.026
133700	1304270	Insufficient Sample		
133701	1304271	27	<0.001	0.027
133702	1304272	20	<0.001	0.020

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, May 29, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
133703	1304273	24	<0.001	0.024
133704 Dup	1304273	20	<0.001	0.020
133705	1304274	14	<0.001	0.014
133706	1304275	18	<0.001	0.018
133707	1304276	20	<0.001	0.020
133708	1304277	16	<0.001	0.016
133709	1304278	28	<0.001	0.028
133710	1304279	16	<0.001	0.016
133711	1304280	<5	<0.001	<0.005
133712	1304281	19	<0.001	0.019
133713	1304282	8	<0.001	0.008
133714	1304283	<5	<0.001	<0.005
133715 Dup	1304283	7	<0.001	0.007
133716	1304284	12	<0.001	0.012
133717	1304285	15	<0.001	0.015
133718	1304286	32	<0.001	0.032
133719	1304287	20	<0.001	0.020
133720	1304288	14	<0.001	0.014
133721	1304289	28	<0.001	0.028
133722	1304290	No Sample Received		
133723	1304291	6	<0.001	0.006
133724	1304292	12	<0.001	0.012
133725	1304293	15	<0.001	0.015
133726 Rep	1304293	14	<0.001	0.014
133727	1304294	145	0.004	0.145
133728	1304295	26	<0.001	0.026
133729	1304296	22	<0.001	0.022
133730	1304297	32	<0.001	0.032
133731	1304298	68	0.002	0.068
133732	1304299	163	0.005	0.163

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, May 29, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
133733	1304300	8	<0.001	0.008
133734	1304301	81	0.002	0.081
133735	1304302	50	0.001	0.050
133736	1304303	8	<0.001	0.008
133737 Dup	1304303	10	<0.001	0.010
133738	1304304	49	0.001	0.049
133739	1304305	24	<0.001	0.024
133740	1304306	83	0.002	0.083
133741	1304307	13	<0.001	0.013
133742	1304308	17	<0.001	0.017
133743	1304309	18	<0.001	0.018
133744	1304310	4967	0.145	4.967
133745	1304311	15	<0.001	0.015
133746	1304312	19	<0.001	0.019
133747	1304313	21	<0.001	0.021
133748 Dup	1304313	19	<0.001	0.019
133749	1304314	17	<0.001	0.017
133750	1304315	24	<0.001	0.024
133751	1304316	25	<0.001	0.025
133752	1304317	84	0.002	0.084
133753	1304318	36	0.001	0.036
133754	1304319	111	0.003	0.111
133755	1304320	9	<0.001	0.009
133756	1304321	144	0.004	0.144
133757	1304322	96	0.003	0.096
133758	1304323	58	0.002	0.058
133759 Dup	1304323	54	0.002	0.054
133760	1304324	20	<0.001	0.020
133761	1304325	30	<0.001	0.030
133762	1304326	52	0.002	0.052

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, May 29, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
133763	1304327	16	<0.001	0.016
133764	1304328	11	<0.001	0.011
133765	1304329	11	<0.001	0.011
133766	1304330	1824	0.053	1.824
133767	1304331	<5	<0.001	<0.005
133768	1304332	<5	<0.001	<0.005
133769	1304333	11	<0.001	0.011
133770 Dup	1304333	<5	<0.001	<0.005
133771	1304334	8	<0.001	0.008
133772	1304335	8	<0.001	0.008
133773	1304336	8	<0.001	0.008
133774	1304337	10	<0.001	0.010
133775	1304338	11	<0.001	0.011
133776	1304339	47	0.001	0.047
133777	1304340	5	<0.001	0.005
133778	1304341	35	0.001	0.035
133779	1304342	7	<0.001	0.007
133780	1304343	10	<0.001	0.010
133781 Dup	1304343	17	<0.001	0.017
133782	1304344	17	<0.001	0.017
133783	1304345	18	<0.001	0.018
133784	1304346	9	<0.001	0.009
133785	1304347	9	<0.001	0.009
133786	1304348	7	<0.001	0.007
133787	1304349	10	<0.001	0.010
133788	1304350	257	0.008	0.257
133789	1304351	11	<0.001	0.011
133790	1304352	10	<0.001	0.010
133791	1304353	<5	<0.001	<0.005
133792 Rep	1304353	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, May 29, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
133793	1304354	<5	<0.001	<0.005
133794	1304355	11	<0.001	0.011
133795	1304356	10	<0.001	0.010
133796	1304357	18	<0.001	0.018
133797	1304358	9	<0.001	0.009
133798	1304359	16	<0.001	0.016
133799	1304360	<5	<0.001	<0.005
133800	1304361	9	<0.001	0.009
133801	1304362	15	<0.001	0.015
133802	1304363	14	<0.001	0.014
133803 Dup	1304363	11	<0.001	0.011
133804	1304364	10	<0.001	0.010
133805	1304365	9	<0.001	0.009
133806	1304366	10	<0.001	0.010
133807	1304367	8	<0.001	0.008
133808	1304368	13	<0.001	0.013
133809	1304369	12	<0.001	0.012
133810	1304370	3893	0.114	3.893
133811	1304371	34	<0.001	0.034
133812	1304372	12	<0.001	0.012
133813	1304373	10	<0.001	0.010
133814 Dup	1304373	9	<0.001	0.009
133815	1304374	10	<0.001	0.010
133816	1304375	12	<0.001	0.012
133817	1304376	12	<0.001	0.012
133818	1304377	11	<0.001	0.011
133819	1304378	13	<0.001	0.013
133820	1304379	11	<0.001	0.011
133821	1304380	7	<0.001	0.007
133822	1304381	13	<0.001	0.013

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, May 29, 2012

Certificate of Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 05/15/2012
 Date Completed: 05/29/2012
 Job #: 201241605
 Reference: TL 12 245
 Sample #: 331

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
133823	1304382	12	<0.001	0.012
133824	1304383	24	<0.001	0.024
133825 Dup	1304383	26	<0.001	0.026
133826	1304384	27	<0.001	0.027

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianiuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Sunday, June 24, 2012


Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/23/2012
 Date Completed: 06/06/2012
 Job #: 201241746
 Reference: TL 12 246
 Sample #: 319

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
146536	1304385	0.014	3	6.76	<2	173	2	<1	5.74	<4	40	172	36	4.88	<0.01	40	1.89	1241	<1	127	4233	<1	1.09	<5	<5	<10	297	6049	2	164	<10	18	58
146537	1304386	0.012	3	7.69	<2	300	2	9	5.28	<4	44	198	36	5.18	<0.01	68	2.32	1045	<1	144	4590	<1	1.02	<5	<5	<10	336	5936	7	174	<10	17	68
146538	1304387	0.006	<1	5.77	<2	291	<2	13	4.24	<4	26	109	18	3.35	<0.01	36	1.61	624	<1	92	2679	<1	0.86	<5	<5	<10	206	4117	3	110	<10	13	29
146539	1304388	0.011	6	6.04	<2	309	<2	10	7.48	<4	32	129	24	4.87	<0.01	42	3.18	1711	<1	99	2674	<1	1.08	<5	<5	<10	233	5011	9	135	<10	14	35
146540	1304389	0.012	3	6.86	<2	345	<2	8	5.11	<4	38	149	32	4.47	<0.01	39	2.34	907	<1	112	2848	<1	1.10	<5	<5	<10	218	5470	6	148	<10	15	44
146541	1304390	1.238	1	4.38	<2	375	2	10	2.33	<4	16	51	22	3.76	<0.01	11	1.46	708	<1	33	2102	<1	0.93	<5	<5	<10	276	2759	10	122	17	17	21
146542	1304391	0.010	2	6.34	<2	366	2	6	5.20	<4	32	132	20	4.30	<0.01	42	2.34	985	<1	105	3605	<1	0.87	<5	<5	<10	234	4737	6	146	<10	16	37
146543	1304392	0.005	2	6.71	<2	254	<2	9	5.76	<4	34	157	69	3.93	<0.01	22	1.47	869	<1	122	2748	<1	0.91	<5	<5	<10	266	5857	5	156	<10	15	12
146544	1304393	<0.005	4	6.93	<2	586	<2	<1	6.49	<4	39	155	44	4.80	<0.01	33	2.25	1018	<1	118	3380	<1	0.94	<5	<5	<10	253	5664	5	154	<10	16	28
146545	1304394	<0.005	1	5.60	<2	501	<2	7	4.73	<4	41	156	37	4.67	<0.01	46	2.25	811	<1	118	1784	<1	0.93	<5	<5	<10	173	5724	6	155	<10	16	39
146546D	1304394	<0.005	<1	6.48	<2	510	<2	6	5.10	<4	41	154	37	4.65	<0.01	45	2.24	805	<1	117	3742	<1	0.90	<5	<5	<10	202	5786	3	157	<10	15	40
146547	1304395	0.010	2	6.48	<2	500	<2	22	4.46	<4	44	161	37	5.87	<0.01	72	2.72	899	<1	121	3360	<1	0.91	<5	<5	<10	198	5845	<2	164	<10	17	62
146548	1304396	0.006	<1	7.46	<2	501	2	3	4.66	<4	43	161	26	5.90	<0.01	73	2.74	914	<1	123	3774	<1	0.98	<5	<5	<10	219	5967	7	164	<10	16	61
146549	1304397	0.013	5	7.09	<2	399	2	18	5.69	<4	41	161	44	4.99	<0.01	57	2.44	950	<1	124	2116	<1	1.03	<5	<5	<10	210	5771	3	156	<10	17	58
146550	1304398	0.045	2	7.29	<2	290	2	4	5.04	<4	49	236	47	6.40	<0.01	70	2.40	1289	<1	162	5327	<1	1.76	<5	<5	<10	231	7615	4	191	<10	21	70
146551	1304399	0.011	5	6.86	<2	300	2	9	7.71	<4	59	305	82	8.02	<0.01	40	2.35	1775	<1	204	5825	3	1.60	<5	<5	<10	277	9668	7	226	<10	26	88
146552	1304400	<0.005	1	5.08	<2	380	<2	6	2.60	<4	16	54	14	3.58	<0.01	12	1.49	705	<1	33	3081	<1	0.99	<5	<5	<10	306	2950	5	123	18	18	32
146553	1304401	0.019	5	5.22	<2	77	2	7	6.99	<4	54	95	103	10.63	<0.01	43	2.93	1592	<1	99	3574	3	1.32	<5	<5	<10	246	5595	<2	322	<10	39	99
146554	1304402	0.014	4	2.58	<2	38	2	<1	4.40	<4	42	78	77	6.67	<0.01	23	1.83	1020	<1	90	1136	<1	1.00	<5	<5	<10	178	4344	<2	299	<10	32	42
146555	1304403	0.009	4	4.46	<2	92	2	12	5.55	<4	51	89	81	8.49	<0.01	34	2.35	1589	<1	95	2254	<1	1.04	<5	<5	<10	212	5312	2	333	<10	36	66

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, June 24, 2012


Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/23/2012
 Date Completed: 06/06/2012
 Job #: 201241746
 Reference: TL 12 246
 Sample #: 319

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
146556	1304404	0.008	4	5.64	<2	60	2	14	6.75	<4	52	105	98	9.25	<0.01	30	2.35	1970	<1	83	2577	<1	1.03	<5	<5	<10	244	6510	6	357	<10	38	72
146557D	1304404	0.010	7	5.70	<2	62	2	5	7.05	<4	55	109	103	9.70	<0.01	31	2.45	2065	<1	88	1577	4	0.94	<5	<5	<10	252	6755	<2	375	<10	39	74
146558	1304405	0.009	7	4.86	<2	147	2	13	5.66	<4	51	93	82	8.63	<0.01	40	2.47	1697	<1	96	2252	<1	1.00	<5	<5	<10	237	5085	5	307	<10	34	77
146559	1304406	0.009	4	5.32	<2	260	2	7	5.92	<4	55	108	105	9.56	<0.01	53	2.67	1817	<1	122	4240	1	1.14	<5	<5	<10	265	5342	2	324	<10	34	93
146560	1304407	0.017	5	3.94	<2	22	2	11	5.11	<4	42	90	72	6.87	<0.01	29	1.85	1164	<1	92	2193	<1	1.23	<5	<5	<10	221	5526	5	213	<10	25	53
146561	1304408	0.011	9	5.69	<2	181	2	16	6.49	<4	57	108	87	10.03	<0.01	50	2.73	2016	<1	108	2830	2	1.05	<5	<5	<10	265	5736	2	331	<10	37	91
146562	1304409	0.010	6	5.92	<2	126	2	<1	6.26	<4	60	96	98	9.90	<0.01	45	2.73	1909	<1	115	2039	3	1.07	<5	<5	<10	275	5630	5	320	<10	35	110
146563	1304410	0.213	<1	<0.01	435	>5000	<2	<1	0.93	<4	6	15	24	3.14	<0.01	3	0.24	<100	3	14	2038	16	1.36	17	<5	<10	127	859	<2	18	44	8	<1
146564	1304411	0.011	5	6.41	<2	111	2	14	7.13	<4	59	114	123	10.61	<0.01	41	2.88	1823	<1	112	2881	3	1.08	<5	<5	<10	301	5743	2	329	<10	38	93
146565	1304412	0.019	4	5.13	<2	127	2	7	6.83	<4	50	127	105	10.19	<0.01	46	3.01	1507	<1	83	3094	<1	1.01	<5	<5	<10	272	5023	<2	335	<10	41	81
146566	1304413	0.010	3	5.35	<2	66	2	16	7.07	<4	51	145	74	10.25	<0.01	33	2.81	1617	<1	86	3599	1	0.97	<5	<5	<10	292	5775	<2	323	<10	38	85
146567	1304414	0.007	7	4.99	<2	32	2	6	6.23	<4	49	150	76	9.46	<0.01	30	2.58	1527	<1	86	1125	2	0.96	<5	<5	<10	280	5338	<2	296	<10	36	74
146568D	1304414	0.008	3	5.73	<2	39	2	6	6.40	<4	50	155	78	9.65	<0.01	33	2.65	1553	<1	89	3470	<1	1.09	6	<5	<10	290	5501	4	301	<10	37	74
146569	1304415	0.010	7	5.32	<2	71	2	8	7.04	<4	51	152	93	9.33	<0.01	31	2.68	1656	<1	94	3699	<1	1.06	<5	<5	<10	289	5613	7	299	<10	37	85
146570	1304416	0.009	4	5.34	<2	80	2	7	6.93	<4	50	147	82	9.08	<0.01	30	2.65	1648	<1	86	5110	<1	1.06	<5	<5	<10	290	5863	5	292	<10	35	82
146571	1304417	0.006	4	5.13	<2	177	2	13	6.88	<4	50	152	95	9.60	<0.01	34	2.65	1752	<1	83	2224	3	0.94	<5	<5	<10	289	5989	6	325	<10	36	75
146572	1304418	0.008	1	5.63	<2	84	2	14	6.79	<4	51	150	95	9.87	<0.01	31	2.67	1857	<1	76	2389	<1	1.07	<5	<5	<10	266	6471	<2	340	<10	38	76
146573	1304419	0.010	7	4.57	<2	52	2	8	6.82	<4	52	129	107	9.81	1.14	27	2.66	1576	<1	68	2855	<1	1.04	<5	<5	<10	266	7621	5	330	<10	37	81
146574	1304420	0.005	<1	5.70	<2	395	2	6	2.69	<4	16	55	14	3.67	<0.01	14	1.54	728	<1	33	2451	<1	0.94	<5	<5	<10	316	3173	9	127	18	18	15
146575	1304421	0.010	8	4.81	<2	<1	2	9	5.71	<4	51	59	102	10.92	<0.01	40	2.78	1451	<1	67	3371	5	1.25	<5	<5	<10	332	6573	<2	378	<10	43	80

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, June 24, 2012

Certificate of Analysis

Treasury Metals Inc
Exchange Tower 130 King St Suite 3680
Toronto, On, CAN
M5X 1B1
Ph#: (416) 599-4133
Fax#: (416) 599-4959
Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 05/23/2012
Date Completed: 06/06/2012
Job #: 201241746
Reference: TL 12 246
Sample #: 319

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
146576	1304422	0.012	4	4.89	<2	35	2	30	7.03	<4	51	102	115	10.19	<0.01	35	2.94	1657	<1	71	1845	1	2.12	<5	<5	<10	244	6516	2	330	<10	40	95
146577	1304423	0.009	4	5.37	<2	195	2	4	6.42	<4	50	124	86	9.44	<0.01	54	3.05	1604	<1	86	3450	<1	1.73	<5	<5	<10	279	5934	<2	294	<10	35	81
146578	1304424	0.006	4	4.70	<2	<1	2	<1	6.49	<4	45	125	60	8.67	<0.01	30	2.80	1397	<1	82	1792	<1	1.28	<5	<5	<10	237	5234	2	255	<10	33	69
146579D	1304424	0.009	1	5.25	<2	4	2	12	7.15	<4	49	137	64	9.48	<0.01	32	2.99	1525	<1	88	2965	2	1.12	<5	<5	<10	269	5523	<2	283	<10	35	77
146580	1304425	0.008	5	5.43	<2	<1	2	12	6.21	<4	48	136	76	9.50	<0.01	38	3.03	1352	<1	96	2599	2	1.14	<5	<5	<10	272	4686	<2	268	<10	37	73
146581	1304426	0.010	1	6.28	<2	78	2	16	6.73	<4	52	153	75	9.63	<0.01	49	3.00	1455	<1	97	3732	6	1.29	<5	<5	<10	292	5272	<2	293	<10	37	93
146582	1304427	0.116	7	6.32	<2	239	2	12	5.09	<4	53	170	81	8.57	<0.01	71	2.80	1331	<1	105	3338	8	1.41	<5	<5	<10	260	5778	7	307	<10	33	91
146583	1304428	0.019	7	5.29	<2	161	2	8	5.90	<4	50	154	97	9.01	<0.01	51	2.91	1455	<1	101	3283	8	1.08	<5	<5	<10	222	4933	<2	306	<10	35	116
146584	1304429	0.008	7	5.50	<2	<1	2	7	5.73	<4	51	98	124	10.77	<0.01	52	2.99	1427	<1	83	2681	6	1.60	<5	<5	<10	286	5146	<2	368	<10	41	80
146585	1304430	5.261	1	3.10	393	1585	2	<1	2.44	<4	13	118	74	3.61	<0.01	12	1.24	480	<1	53	2842	17	1.86	35	<5	<10	203	1782	9	130	15	15	183
146586	1304431	0.009	4	5.19	<2	<1	2	10	5.39	<4	50	86	107	10.29	<0.01	52	2.84	1447	<1	67	980	7	1.63	<5	<5	<10	308	6161	3	334	<10	38	89
146587	1304432	0.017	<1	3.96	<2	475	<2	7	1.44	<4	7	33	<1	1.94	<0.01	62	0.84	428	<1	57	3426	<1	1.10	<5	<5	<10	214	2010	<2	43	<10	6	<1
146588	1304433	0.018	<1	>10.00	<2	308	<2	21	1.07	<4	5	155	321	1.51	0.12	48	0.65	354	<1	73	2588	4	0.73	<5	<5	<10	161	1529	4	45	<10	5	120
146589	1304434	<0.005	<1	3.21	<2	414	<2	<1	1.24	<4	7	57	<1	2.03	<0.01	68	0.66	282	<1	91	1292	<1	1.01	<5	<5	<10	224	1836	<2	47	<10	6	7
146590D	1304434	<0.005	<1	3.14	<2	394	<2	6	1.23	<4	7	58	<1	1.96	<0.01	63	0.63	271	<1	92	1892	<1	0.92	<5	<5	<10	240	1753	<2	45	<10	5	5
146591	1304435	0.008	<1	2.44	<2	291	2	7	3.99	<4	33	83	61	6.18	<0.01	73	1.54	1239	<1	86	3249	3	0.75	<5	<5	<10	251	4907	3	203	<10	22	93
146592	1304436	0.010	5	3.74	<2	235	2	11	4.59	<4	37	89	65	6.69	<0.01	69	1.69	1397	<1	87	3018	<1	0.95	<5	<5	<10	284	5576	2	225	<10	26	89
146593	1304437	0.007	<1	3.34	<2	603	<2	<1	2.61	<4	17	49	10	3.79	<0.01	99	1.36	807	<1	68	2309	<1	0.89	<5	<5	<10	222	3044	<2	105	<10	11	48
146594	1304438	0.006	<1	1.70	<2	781	<2	<1	1.24	<4	6	32	<1	1.76	<0.01	56	0.69	368	<1	60	2616	<1	0.71	<5	<5	<10	166	1841	3	37	<10	5	<1
146595	1304439	<0.005	<1	2.95	<2	596	<2	<1	1.85	<4	6	27	<1	1.77	<0.01	48	0.59	301	<1	55	2457	<1	0.79	<5	<5	<10	217	1945	<2	39	<10	6	2

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
Jason Moore, General Manager

The results included on this report relate only to the items tested.
The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, June 24, 2012


Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/23/2012
 Date Completed: 06/06/2012
 Job #: 201241746
 Reference: TL 12 246
 Sample #: 319

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
146596	1304440	<0.005	<1	1.28	<2	249	<2	6	1.99	<4	14	47	13	3.31	<0.01	4	1.31	643	<1	30	2265	<1	0.56	<5	<5	<10	216	2445	5	110	15	15	19
146597	1304441	0.153	6	3.82	<2	431	2	15	3.35	<4	38	35	69	8.08	<0.01	66	1.83	1183	<1	76	4016	7	1.78	<5	<5	<10	210	4455	<2	246	<10	31	133
146598	1304442	0.011	8	3.04	<2	425	<2	8	4.19	<4	36	33	68	7.04	<0.01	55	1.75	1206	<1	75	3259	<1	0.89	<5	<5	<10	230	4896	7	237	<10	31	73
146599	1304443	<0.005	<1	3.70	<2	813	<2	12	1.81	<4	7	24	<1	1.80	<0.01	42	0.61	291	<1	46	4521	<1	0.77	<5	<5	<10	220	2052	<2	38	<10	6	<1
146600	1304444	0.023	4	1.75	<2	152	2	<1	4.82	<4	44	32	82	8.49	<0.01	34	1.99	1628	<1	77	3892	3	0.73	<5	<5	<10	138	5840	7	302	<10	40	261
146601R	1304444	0.034	7	4.10	<2	180	2	9	5.76	<4	51	33	128	9.50	<0.01	39	2.20	1837	<1	75	3846	6	1.14	<5	<5	<10	202	7149	4	351	<10	45	381
146602	1304445	2.798	14	3.09	<2	204	2	9	1.79	12	43	34	331	9.82	<0.01	66	1.64	1046	<1	84	3791	22	4.50	<5	<5	<10	160	4298	<2	298	35	29	2999
146603	1304446	0.020	5	3.25	<2	180	2	4	5.79	<4	51	37	67	9.73	<0.01	36	2.18	2062	<1	87	1718	4	0.80	<5	<5	<10	184	6011	9	334	<10	46	142
146604	1304447	0.008	2	0.27	<2	<1	<2	8	3.95	<4	36	13	40	7.10	<0.01	14	1.57	1752	<1	49	3216	<1	0.50	<5	<5	<10	113	5452	<2	232	<10	31	74
146605	1304448	0.018	5	2.54	<2	13	2	5	5.01	<4	48	23	143	9.51	<0.01	30	2.05	1981	<1	63	2640	3	1.13	6	<5	<10	132	5577	<2	314	<10	43	98
146606	1304449	0.016	8	2.32	<2	25	2	5	5.11	<4	52	26	131	8.94	<0.01	35	2.01	1907	<1	72	2787	<1	1.15	<5	<5	<10	144	5506	2	305	<10	41	123
146607	1304450	2.091	<1	2.78	<2	300	<2	3	2.06	<4	16	49	22	3.79	<0.01	9	1.41	695	<1	32	3295	4	0.79	<5	<5	<10	227	2644	<2	119	19	16	21
146608	1304451	0.017	3	0.99	<2	32	<2	4	2.52	<4	28	63	102	4.24	<0.01	30	1.03	917	<1	102	1095	<1	0.79	<5	<5	<10	135	4734	<2	221	<10	26	41
146609	1304452	0.103	3	3.73	<2	99	2	9	3.98	7	52	45	118	8.37	<0.01	68	2.15	1486	<1	90	4178	15	1.81	<5	<5	<10	192	5429	<2	332	16	40	1474
146610	1304453	0.042	2	4.61	<2	92	2	7	5.00	<4	56	40	123	9.43	<0.01	63	2.16	1683	<1	73	3756	7	1.78	<5	<5	<10	176	6499	<2	353	<10	43	163
146611	1304454	0.010	3	3.49	<2	<1	2	12	5.48	<4	50	53	67	10.12	<0.01	32	1.82	1678	<1	78	4372	9	0.99	<5	<5	<10	142	4732	<2	345	<10	38	135
146612D	1304454	0.010	5	2.32	<2	<1	2	3	5.34	<4	50	52	70	10.19	<0.01	29	1.79	1686	<1	79	2748	5	0.88	<5	<5	<10	118	4466	<2	342	<10	38	139
146613	1304455	0.007	4	3.89	<2	25	2	10	5.67	<4	55	55	113	10.81	<0.01	38	2.19	1880	<1	87	2262	8	1.21	<5	<5	<10	214	4726	3	353	<10	40	124
146614	1304456	0.017	4	3.80	<2	22	2	6	5.32	<4	53	56	103	10.46	<0.01	36	2.15	1674	<1	87	3008	7	1.18	<5	<5	<10	215	4400	3	341	<10	39	123
146615	1304457	0.011	4	0.28	<2	31	2	10	3.33	<4	35	32	63	7.73	<0.01	29	1.66	1159	<1	61	1672	2	0.79	<5	<5	<10	114	4495	3	272	<10	29	89

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By:  Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, June 24, 2012

Certificate of Analysis

Treasury Metals Inc
Exchange Tower 130 King St Suite 3680
Toronto, On, CAN
M5X 1B1
Ph#: (416) 599-4133
Fax#: (416) 599-4959
Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 05/23/2012
Date Completed: 06/06/2012
Job #: 201241746
Reference: TL 12 246
Sample #: 319

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
146616	1304458	<0.005	<1	2.09	<2	473	<2	3	2.03	<4	11	22	6	2.60	<0.01	54	0.98	714	<1	45	1731	<1	0.85	<5	<5	<10	139	2516	6	65	<10	9	<1
146617	1304459	<0.005	<1	2.43	<2	572	<2	<1	2.68	<4	16	30	40	3.67	<0.01	29	0.98	843	<1	53	1371	<1	1.34	<5	<5	<10	194	2833	5	90	<10	12	30
146618	1304460	0.007	<1	1.82	<2	237	2	3	2.04	<4	15	49	12	3.40	<0.01	7	1.36	670	<1	31	3366	<1	0.71	<5	<5	<10	206	2685	2	110	12	15	12
146619	1304461	0.007	9	2.58	<2	<1	<2	13	5.64	<4	53	46	80	9.95	<0.01	19	2.18	1583	<1	67	2356	<1	0.93	<5	<5	<10	237	6940	<2	299	<10	34	117
146620	1304462	0.012	5	3.79	<2	352	3	14	5.16	<4	45	46	190	10.23	<0.01	42	2.34	2043	<1	68	1697	3	2.48	<5	<5	<10	203	6895	<2	250	<10	30	135
146621	1304463	0.039	4	3.69	<2	171	2	1	4.41	<4	33	39	124	7.20	<0.01	48	2.20	1387	<1	53	4558	10	2.28	<5	<5	<10	201	5233	3	208	<10	25	99
146622	1304464	0.030	4	2.90	<2	127	2	6	5.21	<4	54	60	93	9.72	<0.01	37	2.13	1921	<1	75	5823	8	1.64	<5	<5	<10	175	7203	<2	316	<10	38	133
146623D	1304464	0.041	7	4.12	<2	141	2	16	5.43	<4	54	59	88	9.62	<0.01	39	2.17	1926	<1	71	3047	7	1.74	<5	<5	<10	194	7434	4	325	<10	39	127
146624	1304465	0.020	3	1.36	<2	675	<2	7	2.17	<4	33	46	57	5.13	<0.01	38	1.33	885	<1	77	757	3	1.83	<5	<5	<10	123	4632	2	156	<10	17	50
146625	1304466	0.006	<1	4.95	<2	1115	<2	17	2.32	<4	10	51	8	2.26	<0.01	39	1.14	453	<1	63	3929	5	1.20	<5	<5	<10	231	2050	8	51	<10	7	35
146626	1304467	0.006	<1	4.31	<2	656	2	15	2.20	<4	25	72	92	5.74	<0.01	47	1.36	619	<1	108	2062	7	3.05	5	<5	<10	310	2360	3	59	<10	8	287
146627	1304468	<0.005	<1	2.86	<2	926	<2	9	1.83	<4	9	41	<1	2.22	<0.01	34	0.86	355	<1	71	1824	<1	0.71	<5	<5	<10	248	2391	2	49	<10	6	11
146628	1304469	<0.005	<1	0.73	<2	823	<2	7	1.22	<4	8	39	<1	2.06	<0.01	29	0.86	345	<1	71	1456	<1	0.63	<5	<5	<10	221	2225	<2	44	<10	5	<1
146629	1304470	0.282	<1	<0.01	407	>5000	<2	7	0.80	<4	6	13	21	2.90	<0.01	<1	0.21	<100	2	13	1955	16	1.12	22	<5	<10	141	815	<2	16	45	7	<1
146630	1304471	<0.005	<1	1.88	<2	697	<2	13	1.97	<4	9	29	<1	2.04	<0.01	19	0.74	351	<1	47	492	<1	0.80	<5	<5	<10	318	2341	<2	46	<10	6	8
146631	1304472	<0.005	<1	2.18	<2	1948	<2	<1	1.83	<4	8	27	<1	1.99	<0.01	23	0.94	396	<1	50	1542	<1	0.81	<5	<5	<10	301	2303	2	46	<10	6	<1
146632	1304473	<0.005	1	3.95	<2	2842	<2	8	2.31	<4	9	25	<1	2.02	<0.01	20	0.99	398	<1	45	2963	<1	0.98	<5	<5	<10	391	2362	<2	47	<10	6	<1
146633	1304474	<0.005	1	2.96	<2	1816	<2	3	1.83	<4	7	32	3	1.97	<0.01	24	0.95	371	<1	52	3669	<1	0.74	<5	<5	<10	263	2318	<2	46	<10	6	<1
146634D	1304474	<0.005	1	5.23	<2	2113	<2	8	2.20	<4	8	28	3	1.89	<0.01	27	0.96	359	<1	47	3469	<1	1.00	<5	<5	<10	326	2322	<2	46	<10	6	<1
146635	1304475	<0.005	<1	3.27	<2	552	<2	5	2.05	<4	9	32	5	2.00	<0.01	19	0.78	372	<1	56	2801	3	0.84	<5	<5	<10	364	2276	<2	46	<10	6	15

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
Jason Moore, General Manager

The results included on this report relate only to the items tested.
The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, June 24, 2012


Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/23/2012
 Date Completed: 06/06/2012
 Job #: 201241746
 Reference: TL 12 246
 Sample #: 319

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
146636	1304476	<0.005	<1	1.25	<2	493	<2	<1	1.87	<4	9	33	4	2.04	<0.01	17	0.77	387	<1	58	2786	<1	0.60	<5	<5	<10	293	2292	<2	47	<10	5	16
146637	1304477	<0.005	<1	2.71	<2	603	<2	4	1.73	<4	8	28	4	1.97	<0.01	20	0.76	351	<1	49	4092	2	0.75	<5	<5	<10	287	2229	<2	44	<10	5	6
146638	1304478	<0.005	<1	3.61	<2	415	<2	3	1.99	<4	8	31	4	2.06	<0.01	28	0.88	383	<1	55	2751	4	0.75	<5	<5	<10	358	2307	<2	47	<10	6	12
146639	1304479	<0.005	<1	1.84	<2	283	<2	16	1.50	<4	15	32	35	3.96	<0.01	27	1.00	611	<1	60	1351	8	1.53	<5	<5	<10	233	2141	2	47	<10	6	236
146640	1304480	<0.005	<1	3.61	<2	313	<2	8	2.27	<4	15	49	12	3.42	<0.01	10	1.40	677	<1	31	1716	<1	0.80	<5	<5	<10	257	2816	<2	114	14	16	14
146641	1304481	<0.005	<1	2.75	<2	26	<2	14	5.14	<4	35	168	64	5.84	<0.01	14	2.87	1485	<1	83	3302	3	0.75	<5	<5	<10	221	3589	6	216	<10	16	50
146642	1304482	<0.005	<1	3.67	<2	28	2	10	5.68	<4	29	228	48	4.90	<0.01	10	2.61	1313	<1	75	4559	<1	0.90	<5	<5	<10	242	3301	6	193	11	14	35
146643	1304483	<0.005	1	5.50	<2	65	2	13	6.31	<4	39	334	55	6.45	<0.01	18	3.23	1569	<1	85	4919	3	1.14	<5	<5	<10	273	3466	4	220	<10	16	61
146644	1304484	<0.005	<1	2.57	<2	35	<2	5	4.99	<4	32	213	26	5.48	<0.01	15	2.78	1295	<1	77	2469	4	0.71	<5	<5	<10	253	3040	10	186	121	12	37
146645D	1304484	<0.005	2	3.84	<2	48	<2	11	5.46	<4	34	221	26	5.81	<0.01	18	2.98	1379	<1	77	1030	6	0.79	<5	<5	<10	283	3315	<2	203	146	14	44
146646	1304485	<0.005	<1	3.78	<2	417	2	2	2.70	<4	21	133	41	4.08	<0.01	27	1.49	882	<1	77	2969	10	1.05	<5	<5	<10	299	2210	3	116	<10	10	68
146647	1304486	<0.005	<1	4.32	<2	748	2	4	1.35	<4	21	140	21	4.17	<0.01	36	1.64	526	<1	105	2097	8	0.98	<5	<5	<10	230	2386	<2	105	<10	12	62
146648	1304487	<0.005	<1	4.48	<2	995	2	11	1.67	<4	17	109	32	3.50	<0.01	29	1.36	474	<1	101	2828	3	1.03	<5	<5	<10	281	2534	<2	81	<10	10	13
146649	1304488	0.005	<1	3.24	<2	1670	<2	1	2.24	<4	10	27	<1	2.43	<0.01	12	1.27	446	<1	52	3851	<1	0.92	<5	<5	<10	307	2183	<2	47	<10	6	<1
146650	1304489	<0.005	<1	3.41	<2	1973	<2	3	1.80	<4	11	49	5	2.33	<0.01	17	1.07	363	<1	71	1273	2	0.88	<5	<5	<10	296	1961	2	52	<10	7	<1
146651	1304490	5.134	<1	2.73	361	1526	2	6	2.21	<4	11	109	71	3.42	<0.01	11	1.16	447	<1	46	2022	21	1.62	32	<5	<10	183	1689	4	120	<10	14	179
146652	1304491	<0.005	<1	3.10	<2	805	<2	2	1.56	<4	9	46	9	2.25	0.08	12	0.96	345	<1	73	3530	<1	0.82	<5	<5	<10	221	1629	3	48	<10	6	18
146653	1304492	0.005	<1	1.30	<2	551	<2	11	0.93	<4	11	66	14	2.66	0.03	15	1.07	365	<1	81	2124	3	0.70	<5	<5	<10	138	1471	<2	58	<10	6	46
146654	1304493	<0.005	<1	4.19	8	256	2	3	1.15	<4	20	161	32	4.10	0.04	35	1.61	642	<1	119	2186	16	0.98	<5	<5	<10	165	2062	3	86	<10	12	2
146655	1304494	0.005	<1	5.61	16	317	2	11	1.23	<4	25	167	24	4.82	<0.01	45	1.85	630	<1	119	3536	18	0.98	<5	<5	<10	163	2207	<2	116	<10	12	17

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, June 24, 2012


Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/23/2012
 Date Completed: 06/06/2012
 Job #: 201241746
 Reference: TL 12 246
 Sample #: 319

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
146656D	1304494	0.005	<1	6.92	13	334	3	16	1.42	<4	26	172	25	4.89	<0.01	48	1.90	662	<1	123	2882	15	1.26	<5	<5	<10	182	2305	2	120	<10	13	32
146657	1304495	0.005	<1	6.65	<2	347	2	11	1.30	<4	24	165	40	4.57	<0.01	41	1.78	563	<1	110	2999	17	1.26	<5	<5	<10	183	2727	<2	111	<10	12	33
146658	1304496	<0.005	<1	6.42	<2	335	2	14	1.19	<4	23	156	38	4.45	<0.01	42	1.75	540	<1	106	1194	16	1.20	<5	<5	<10	175	2697	7	109	<10	12	28
146659	1304497	0.006	<1	5.69	3	536	2	12	0.80	<4	28	169	35	5.26	<0.01	45	2.02	536	<1	128	3375	16	1.04	<5	<5	<10	173	3304	2	136	<10	11	43
146660	1304498	<0.005	<1	6.87	<2	564	2	19	0.88	<4	28	170	41	5.13	<0.01	48	2.04	537	<1	134	2651	17	1.25	<5	<5	<10	165	3406	<2	132	<10	11	33
146661	1304499	<0.005	<1	6.89	<2	596	3	7	0.93	<4	29	176	47	5.36	<0.01	45	2.06	558	<1	131	3281	13	1.15	<5	<5	<10	189	3305	<2	140	<10	11	20
146662	1304500	<0.005	<1	4.80	<2	352	<2	6	2.41	<4	15	51	13	3.38	<0.01	11	1.43	673	<1	31	1347	1	0.91	<5	<5	<10	284	2960	<2	116	20	17	26
146663	1304501	<0.005	<1	5.81	<2	434	2	11	0.93	<4	27	179	38	4.90	<0.01	37	1.93	512	<1	147	3470	15	1.17	<5	<5	<10	175	3226	<2	125	<10	11	<1
146664	1304502	0.005	<1	7.88	<2	453	2	19	1.40	<4	28	200	48	5.23	<0.01	40	2.07	662	<1	155	1755	19	1.28	<5	<5	<10	248	3469	4	135	<10	13	<1
146665	1304503	<0.005	<1	7.25	<2	497	2	10	0.76	<4	30	203	48	5.60	<0.01	36	2.16	546	<1	152	1791	14	1.18	<5	<5	<10	182	3181	<2	147	<10	12	<1
146666	1304504	0.006	<1	4.10	<2	501	2	7	0.60	<4	29	192	48	5.37	<0.01	32	2.01	497	<1	159	3155	13	0.83	<5	<5	<10	149	3222	<2	138	<10	10	<1
146667R	1304504	<0.005	<1	4.27	<2	509	2	3	0.68	<4	29	202	48	5.49	<0.01	31	2.03	512	<1	170	1996	14	0.83	<5	<5	<10	162	3217	<2	140	<10	10	<1
146668	1304505	<0.005	<1	6.41	<2	635	3	11	0.78	<4	30	191	48	5.50	<0.01	38	2.04	447	<1	156	3297	16	1.15	<5	<5	<10	210	3668	2	147	<10	10	5
146669	1304506	0.006	2	6.29	<2	415	2	8	1.09	<4	24	179	35	4.61	<0.01	34	1.80	577	<1	142	4250	12	1.13	<5	<5	<10	192	2828	<2	112	<10	12	<1
146670	1304507	0.005	<1	7.93	<2	463	3	8	1.28	<4	24	180	40	4.65	<0.01	41	1.88	464	<1	159	5216	17	1.33	<5	<5	<10	224	3149	6	109	<10	12	<1
146671	1304508	<0.005	1	7.12	<2	551	2	10	1.44	<4	23	179	40	4.44	<0.01	35	1.72	637	<1	123	4989	16	1.09	5	<5	<10	226	2910	<2	107	<10	14	13
146672	1304509	<0.005	<1	7.22	<2	485	2	9	1.19	<4	26	178	39	4.91	<0.01	41	1.95	708	<1	129	2810	19	1.13	<5	<5	<10	232	3233	3	121	<10	14	20
146673	1304510	2.040	<1	4.73	<2	363	2	11	2.33	<4	16	52	22	3.89	<0.01	13	1.49	723	<1	34	2533	<1	0.82	<5	<5	<10	267	2951	2	124	20	17	23
146674	1304511	0.012	<1	7.25	<2	461	2	19	1.00	<4	26	184	33	4.77	<0.01	49	1.93	555	<1	119	768	13	1.25	<5	<5	<10	193	3205	2	126	<10	12	27
146675	1304512	<0.005	1	6.20	<2	446	2	<1	1.32	<4	19	155	38	3.82	<0.01	30	1.51	502	<1	107	1235	11	1.14	<5	<5	<10	226	2518	4	88	<10	11	33

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, June 24, 2012

Certificate of Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 05/23/2012
 Date Completed: 06/06/2012
 Job #: 201241746
 Reference: TL 12 246
 Sample #: 319

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
146676	1304513	0.007	<1	7.04	<2	761	2	17	1.20	<4	23	180	43	4.39	<0.01	35	1.71	508	<1	134	1810	16	1.22	<5	<5	<10	224	2726	<2	111	<10	13	33
146677	1304514	0.005	<1	6.38	<2	831	2	11	1.76	<4	20	162	40	4.03	<0.01	31	1.61	620	<1	107	1499	13	1.13	<5	<5	<10	291	2741	4	91	<10	13	22
146678D	1304514	<0.005	<1	5.10	<2	838	2	14	1.60	<4	21	169	43	4.18	<0.01	28	1.61	626	<1	112	1740	13	0.96	<5	<5	<10	274	2607	2	92	<10	12	24
146679	1304515	0.005	<1	8.67	<2	918	3	9	1.67	<4	29	206	55	5.37	<0.01	47	2.07	708	<1	130	1974	17	1.59	<5	<5	<10	279	3473	6	117	<10	16	37
146680	1304516	0.007	<1	7.78	<2	894	2	15	1.64	<4	27	201	50	5.03	<0.01	41	1.97	685	<1	124	802	15	1.37	<5	<5	<10	277	3352	3	112	<10	15	29
146681	1304517	<0.005	1	6.36	<2	572	2	14	1.37	<4	21	159	33	3.71	<0.01	31	1.52	498	<1	93	4231	15	1.21	<5	<5	<10	252	2727	2	84	<10	11	23
146682	1304518	<0.005	<1	7.87	<2	619	2	13	1.15	<4	27	172	44	4.98	<0.01	46	1.88	551	<1	129	1229	16	1.31	<5	<5	<10	249	3392	<2	117	<10	13	26
146683	1304519	<0.005	<1	6.38	<2	528	2	14	1.01	<4	23	163	28	4.56	<0.01	40	1.77	533	<1	115	1213	10	1.06	<5	<5	<10	219	2977	4	111	<10	13	24
146684	1304520	<0.005	<1	6.27	<2	342	2	8	2.60	<4	16	54	13	3.53	<0.01	18	1.54	703	<1	29	2001	<1	1.00	5	<5	<10	284	3066	<2	119	17	18	13
146685	1304521	0.006	<1	5.64	<2	469	2	15	1.14	<4	22	159	36	4.28	<0.01	33	1.57	526	<1	113	3208	13	0.98	<5	<5	<10	233	2947	<2	102	<10	12	16
146686	1304522	0.008	<1	7.23	<2	459	3	14	1.42	<4	25	179	37	4.76	<0.01	41	1.80	626	<1	127	1821	12	1.19	<5	<5	<10	239	3072	2	120	<10	13	11
146687	1304523	0.006	<1	7.45	<2	409	3	15	1.47	<4	25	172	39	4.51	<0.01	38	1.74	528	<1	103	2477	15	1.25	<5	<5	<10	262	2515	<2	114	<10	12	3
146688	1304524	0.008	<1	6.53	<2	455	2	14	1.25	<4	25	189	41	4.97	<0.01	40	1.81	564	<1	128	3486	17	1.14	<5	<5	<10	244	3025	3	122	<10	13	1
146689D	1304524	0.007	<1	7.26	<2	448	2	5	1.31	<4	25	188	40	4.86	<0.01	42	1.80	549	<1	125	3802	19	1.32	<5	<5	<10	247	2973	<2	120	<10	13	<1
146690	1304525	0.005	<1	4.64	<2	314	2	1	1.19	<4	21	173	34	4.05	<0.01	30	1.50	524	<1	113	176	13	0.82	<5	<5	<10	251	2345	2	95	<10	11	13
146691	1304526	0.006	<1	6.57	<2	287	2	21	1.25	<4	21	168	37	4.05	<0.01	38	1.58	493	<1	88	<100	17	1.22	<5	<5	<10	269	2198	2	92	<10	12	23
146692	1304527	0.007	<1	6.88	<2	367	2	11	1.33	<4	22	168	35	4.21	<0.01	35	1.61	558	<1	101	1833	16	1.17	<5	<5	<10	277	2691	5	98	<10	12	22
146693	1304528	0.007	<1	6.41	<2	447	2	12	1.41	<4	22	171	32	4.17	<0.01	37	1.55	530	<1	119	1045	13	1.14	<5	<5	<10	282	2778	5	102	<10	12	27
146694	1304529	0.005	<1	6.26	<2	493	2	<1	0.94	<4	24	179	39	4.57	<0.01	43	1.72	510	<1	110	3312	15	1.21	<5	<5	<10	219	2905	3	109	<10	12	30
146695	1304530	0.229	<1	<0.01	416	>5000	<2	8	0.92	<4	6	13	22	2.94	<0.01	5	0.26	<100	4	11	843	11	1.18	16	<5	<10	144	969	<2	16	46	8	<1

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, June 24, 2012


Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/23/2012
 Date Completed: 06/06/2012
 Job #: 201241746
 Reference: TL 12 246
 Sample #: 319

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
146696	1304531	0.006	<1	7.25	<2	613	2	18	0.83	<4	26	178	35	4.68	<0.01	47	1.79	511	<1	113	2763	10	1.16	<5	<5	<10	206	3078	3	123	<10	11	33
146697	1304532	<0.005	<1	6.82	<2	496	2	<1	1.18	<4	22	171	28	4.22	<0.01	47	1.64	581	<1	112	950	12	1.21	<5	<5	<10	252	2877	5	102	<10	12	20
146698	1304533	0.006	<1	5.87	<2	428	2	10	1.17	<4	21	161	35	3.98	<0.01	46	1.45	521	<1	116	2683	10	1.20	5	<5	<10	271	2479	<2	91	28	12	11
146699	1304534	0.007	<1	4.88	<2	267	2	8	1.25	<4	15	162	29	3.21	<0.01	37	1.19	470	<1	103	3508	11	1.28	<5	<5	<10	340	2166	2	72	<10	11	11
146700D	1304534	0.007	<1	4.35	<2	266	2	2	1.17	<4	15	161	28	3.18	<0.01	36	1.16	458	<1	105	2102	13	1.11	<5	<5	<10	327	2055	<2	71	<10	11	7
146701	1304535	0.006	<1	6.65	<2	394	2	1	1.45	<4	18	163	34	3.58	<0.01	47	1.34	581	<1	101	2283	13	1.28	<5	<5	<10	329	2553	5	82	<10	13	18
146702	1304536	<0.005	<1	4.94	<2	391	2	<1	1.24	<4	19	171	38	3.73	<0.01	44	1.33	592	<1	114	1992	16	1.06	<5	<5	<10	298	2268	<2	82	<10	13	20
146703	1304537	0.006	<1	4.95	<2	532	2	5	0.92	<4	20	174	34	3.79	<0.01	49	1.35	434	<1	129	964	15	0.98	<5	<5	<10	266	2448	6	91	<10	11	21
146704	1304538	0.006	<1	6.56	<2	575	2	2	1.38	<4	22	191	32	4.28	<0.01	60	1.52	578	1	145	2267	15	1.11	<5	<5	<10	319	2798	<2	98	<10	12	26
146705	1304539	0.005	<1	6.62	<2	613	3	5	1.06	<4	21	172	29	4.08	<0.01	64	1.49	555	<1	129	2036	18	1.10	<5	<5	<10	264	2859	3	102	<10	11	26
146706	1304540	0.008	<1	5.49	<2	329	2	3	2.51	<4	15	53	12	3.52	<0.01	15	1.51	697	<1	29	2328	<1	0.97	<5	<5	<10	274	2990	3	117	15	18	12
146707	1304541	<0.005	<1	6.13	<2	518	2	10	1.14	<4	20	158	31	3.82	<0.01	62	1.43	542	<1	114	2838	11	1.23	<5	<5	<10	278	2694	4	86	<10	11	24
146708	1304542	<0.005	<1	5.69	<2	284	5	11	0.93	<4	14	135	23	3.06	<0.01	55	1.15	627	<1	92	1315	12	1.21	<5	<5	<10	258	2073	4	66	<10	10	15
146709	1304543	0.006	<1	6.43	<2	552	2	8	1.06	<4	21	172	46	4.07	<0.01	68	1.48	533	<1	124	927	14	1.27	<5	<5	<10	274	2772	6	96	<10	12	19
146710	1304544	<0.005	<1	6.19	<2	467	2	8	1.19	<4	20	156	32	3.78	<0.01	64	1.42	538	<1	107	2219	11	1.09	<5	<5	<10	302	2740	<2	91	<10	12	18
146711D	1304544	<0.005	<1	5.96	<2	494	2	10	1.18	<4	22	162	35	3.96	<0.01	65	1.46	560	<1	106	3472	13	1.10	<5	<5	<10	310	2769	<2	95	<10	12	21
146712	1304545	<0.005	<1	5.49	<2	495	2	13	1.15	<4	20	153	35	3.53	<0.01	60	1.40	473	<1	97	1654	16	1.01	<5	<5	<10	298	2590	4	90	<10	10	18
146713	1304546	0.005	<1	6.35	<2	662	2	7	0.66	<4	23	151	26	4.42	<0.01	76	1.83	437	<1	110	895	16	1.08	<5	<5	<10	213	2981	2	106	<10	11	19
146714	1304547	<0.005	<1	5.35	<2	556	2	12	1.00	<4	22	167	36	4.39	<0.01	63	1.65	594	<1	110	4310	17	0.85	8	<5	<10	260	2852	5	108	<10	12	10
146715	1304548	<0.005	1	6.14	<2	632	2	5	1.34	<4	22	175	43	4.15	<0.01	56	1.60	496	<1	126	2042	16	1.02	<5	<5	<10	393	2701	11	107	<10	13	1

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By:  Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, June 24, 2012


Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/23/2012
 Date Completed: 06/06/2012
 Job #: 201241746
 Reference: TL 12 246
 Sample #: 319

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
146716	1304549	<0.005	<1	5.48	<2	585	2	9	1.01	<4	22	172	37	4.19	<0.01	51	1.57	491	<1	120	864	14	0.98	<5	<5	<10	327	2779	2	98	<10	11	8
146717	1304550	5.315	<1	4.55	377	1131	<2	11	2.45	<4	12	118	69	3.56	<0.01	17	1.27	471	3	50	4114	19	1.77	37	<5	<10	198	1924	8	126	<10	16	176
146718	1304551	0.006	<1	5.15	<2	301	2	10	1.17	<4	14	131	29	3.03	<0.01	37	1.21	433	<1	109	2806	12	1.07	<5	<5	<10	356	2083	6	63	<10	9	6
146719	1304552	0.005	<1	5.36	<2	457	2	10	1.00	<4	20	156	34	3.78	<0.01	43	1.50	533	<1	111	1548	14	0.98	<5	<5	<10	279	2607	<2	89	<10	11	11
146720	1304553	0.006	<1	5.48	<2	644	2	9	0.65	<4	23	176	35	4.46	<0.01	45	1.67	476	<1	128	1823	15	1.07	<5	<5	<10	172	2752	<2	107	<10	11	21
146721	1304554	0.008	<1	7.47	<2	677	2	7	1.05	<4	24	189	40	4.62	<0.01	47	1.78	496	<1	125	2243	21	1.22	<5	<5	<10	230	2856	2	118	<10	12	46
146722D	1304554	0.009	<1	6.72	<2	666	2	6	0.94	<4	24	184	39	4.59	<0.01	46	1.76	486	<1	120	4057	14	1.14	<5	<5	<10	214	2887	<2	117	<10	11	39
146723	1304555	0.008	<1	6.90	<2	462	2	15	1.33	<4	20	166	34	3.86	<0.01	45	1.58	509	<1	94	2824	16	1.47	<5	<5	<10	273	2647	5	89	<10	12	26
146724	1304556	0.005	<1	6.78	<2	462	2	8	1.33	<4	20	188	35	3.95	<0.01	44	1.56	511	<1	128	3577	18	1.23	<5	<5	<10	270	2579	4	89	<10	12	24
146725	1304557	0.007	<1	7.05	<2	419	2	8	1.28	<4	19	165	32	3.67	<0.01	42	1.56	426	<1	104	2862	15	1.29	<5	<5	<10	274	2526	<2	84	<10	12	19
146726	1304558	0.008	<1	6.26	<2	391	2	5	1.46	<4	17	156	33	3.53	<0.01	37	1.45	542	<1	102	1218	18	1.27	<5	<5	<10	287	2477	<2	80	<10	13	13
146727	1304559	0.005	<1	6.42	<2	545	3	9	0.93	<4	24	169	36	4.50	<0.01	46	1.75	452	<1	132	4017	15	1.20	<5	<5	<10	234	3183	3	111	<10	12	10
146728	1304560	<0.005	<1	6.14	<2	387	<2	6	2.63	<4	15	55	13	3.53	<0.01	15	1.52	699	<1	29	2191	<1	1.12	<5	<5	<10	306	3018	10	122	20	18	17
146729	1304561	0.008	<1	6.56	<2	489	3	15	1.22	<4	22	175	35	4.18	<0.01	43	1.63	491	<1	132	<100	16	1.21	5	<5	<10	254	2860	<2	102	<10	12	9
146730	1304562	<0.005	<1	6.45	<2	385	2	16	1.40	<4	19	169	36	3.81	<0.01	37	1.58	463	<1	109	3263	17	1.20	<5	<5	<10	266	2588	2	86	<10	12	14
146731	1304563	0.008	<1	6.77	<2	407	2	15	1.47	<4	19	172	34	3.76	<0.01	38	1.54	482	<1	116	2264	16	1.24	<5	<5	<10	278	2604	3	86	<10	12	20
146732	1304564	0.005	<1	6.93	<2	454	2	8	1.17	<4	23	174	36	4.37	<0.01	42	1.70	503	<1	120	1649	17	1.32	<5	<5	<10	247	2919	<2	102	<10	13	11
146733R	1304564	0.007	<1	6.36	<2	467	2	12	1.09	<4	22	176	32	4.37	<0.01	39	1.65	487	<1	128	994	18	1.13	<5	<5	<10	245	3137	<2	106	<10	12	12
146734	1304565	0.008	<1	7.88	<2	723	3	4	0.80	<4	33	206	36	5.70	<0.01	56	2.09	453	2	159	1199	19	1.27	<5	<5	<10	194	4062	<2	158	<10	13	36
146735	1304566	0.008	<1	7.06	<2	472	2	8	1.49	<4	25	174	49	4.64	<0.01	38	1.83	698	<1	129	3003	17	1.15	<5	<5	<10	268	3137	3	113	<10	14	2

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, June 24, 2012


Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/23/2012
 Date Completed: 06/06/2012
 Job #: 201241746
 Reference: TL 12 246
 Sample #: 319

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
146736	1304567	0.006	<1	6.93	<2	364	2	15	1.41	<4	21	164	35	4.18	<0.01	35	1.61	559	<1	123	2414	16	1.30	<5	<5	<10	273	2879	8	97	<10	13	1
146737	1304568	0.005	<1	5.69	<2	481	2	5	1.20	<4	26	179	42	5.00	<0.01	37	1.83	560	<1	138	2416	14	1.02	<5	<5	<10	262	3084	<2	127	<10	13	<1
146738	1304569	0.007	2	7.12	<2	418	3	10	1.68	<4	22	185	31	4.43	<0.01	36	1.64	662	<1	145	2846	14	1.18	<5	<5	<10	304	2926	8	106	<10	15	8
146739	1304570	1.905	<1	4.26	<2	345	<2	3	2.13	<4	15	46	19	3.44	<0.01	11	1.37	641	<1	28	2344	<1	0.85	<5	<5	<10	256	2508	<2	112	17	16	14
146740	1304571	0.010	1	6.75	<2	627	2	17	0.84	<4	25	169	48	4.76	<0.01	38	1.56	475	<1	113	2208	15	1.13	<5	<5	<10	244	3044	2	124	<10	13	20
146741	1304572	0.006	1	6.22	<2	330	2	11	1.73	<4	17	152	13	3.54	<0.01	32	1.38	543	<1	120	4626	15	1.15	<5	<5	<10	365	2481	4	89	<10	13	11
146742	1304573	0.008	<1	7.12	<2	531	3	8	1.12	<4	29	199	39	5.45	<0.01	45	1.87	549	<1	150	3382	18	1.09	<5	<5	<10	296	3222	<2	133	<10	14	17
146743	1304574	0.007	<1	7.78	<2	612	3	15	0.86	<4	30	186	68	5.43	<0.01	47	1.85	510	<1	122	1392	14	1.21	<5	<5	<10	223	2961	<2	138	<10	13	54
146744D	1304574	0.005	<1	6.48	<2	523	2	17	0.74	<4	27	162	58	4.77	<0.01	40	1.64	454	<1	109	2144	13	1.19	<5	<5	<10	204	2668	2	120	<10	12	40
146745	1304575	<0.005	<1	7.73	<2	447	2	17	1.56	<4	23	190	24	4.62	<0.01	44	1.79	573	<1	127	1109	18	1.09	<5	<5	<10	327	3064	<2	109	<10	13	20
146746	1304576	<0.005	<1	8.27	<2	456	2	16	1.55	<4	23	162	27	4.51	<0.01	47	1.82	556	<1	101	923	17	1.32	<5	<5	<10	316	3143	5	106	<10	13	19
146747	1304577	<0.005	<1	6.75	<2	420	2	7	1.96	<4	21	148	38	3.81	<0.01	36	1.57	590	<1	78	1281	19	1.17	<5	<5	<10	372	2861	2	91	<10	13	15
146748	1304578	<0.005	<1	7.46	<2	791	2	7	1.11	<4	27	190	55	5.05	<0.01	42	1.71	613	<1	117	2195	13	1.26	5	<5	<10	260	3419	<2	137	<10	15	37
146749	1304579	0.006	<1	7.22	<2	682	2	8	0.78	<4	28	175	46	4.92	<0.01	35	1.69	427	<1	129	4821	10	1.36	<5	<5	<10	203	2888	<2	128	<10	12	42
146750	1304580	<0.005	<1	6.73	<2	400	2	11	2.72	<4	16	58	14	3.60	<0.01	18	1.56	717	<1	30	2919	<1	1.29	<5	<5	<10	320	3199	3	125	22	18	16
146751	1304581	<0.005	<1	8.58	<2	757	3	12	0.97	<4	29	193	46	5.18	<0.01	52	1.84	511	<1	129	3515	13	1.37	5	<5	<10	266	3201	4	139	<10	14	62
146752	1304582	0.005	<1	6.96	<2	561	3	9	1.57	<4	23	179	31	4.27	<0.01	39	1.64	536	<1	129	3482	16	1.30	<5	<5	<10	327	2867	6	107	<10	14	23
146753	1304583	<0.005	<1	7.12	<2	807	2	14	1.06	<4	23	159	39	4.36	<0.01	37	1.53	431	<1	121	2884	16	1.47	5	<5	<10	279	2848	8	111	<10	11	58
146754	1304584	<0.005	<1	6.71	<2	635	2	7	1.72	<4	25	184	57	4.40	<0.01	36	1.62	544	<1	133	1943	15	1.56	<5	<5	<10	296	2914	4	101	<10	13	35
146755D	1304584	0.005	<1	6.46	<2	611	2	5	1.67	<4	24	183	56	4.33	<0.01	36	1.60	534	<1	136	1367	16	1.56	<5	<5	<10	287	2808	<2	98	<10	12	33

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, June 24, 2012

Certificate of Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 05/23/2012
 Date Completed: 06/06/2012
 Job #: 201241746
 Reference: TL 12 246
 Sample #: 319

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
146756	1304585	0.008	1	5.55	<2	468	2	20	2.58	<4	24	220	39	3.36	<0.01	29	1.61	547	<1	119	2453	13	1.24	7	<5	<10	301	2797	2	91	<10	16	13
146757	1304586	<0.005	<1	6.42	<2	719	2	2	2.05	<4	22	189	39	3.91	<0.01	33	1.56	524	<1	119	3312	14	1.32	<5	<5	<10	332	3069	<2	98	<10	12	20
146758	1304587	0.005	<1	6.10	<2	606	2	5	1.65	<4	20	160	30	3.66	<0.01	31	1.52	478	<1	92	898	17	1.27	<5	<5	<10	276	2848	5	83	<10	11	30
146759	1304588	0.006	<1	5.87	<2	559	2	15	1.53	<4	21	169	39	3.93	<0.01	32	1.56	486	<1	88	1162	15	1.35	<5	<5	<10	258	2821	3	85	<10	12	32
146760	1304589	<0.005	2	5.96	<2	548	2	7	1.60	<4	17	151	30	3.47	<0.01	31	1.44	474	<1	92	3619	16	1.25	<5	<5	<10	248	2657	<2	78	<10	13	19
146761	1304590	0.252	<1	<0.01	405	>5000	<2	<1	0.84	<4	6	16	21	2.88	<0.01	3	0.23	<100	3	12	1610	13	1.29	17	<5	<10	133	919	<2	16	44	8	<1
146762	1304591	0.006	<1	7.03	<2	590	2	17	1.88	<4	20	171	41	3.82	<0.01	34	1.57	523	<1	121	737	20	1.38	<5	<5	<10	288	3027	6	91	<10	15	30
146763	1304592	0.005	1	6.09	<2	434	2	16	1.81	<4	19	164	32	3.67	<0.01	30	1.42	510	<1	103	2397	15	1.21	<5	<5	<10	285	2861	3	86	<10	14	23
146764	1304593	<0.005	<1	6.31	<2	428	2	2	1.72	<4	21	166	35	3.81	<0.01	33	1.42	513	<1	120	3750	20	1.21	<5	<5	<10	269	2868	<2	89	<10	13	24
146765	1304594	0.006	<1	7.48	<2	517	2	<1	1.34	<4	24	176	39	4.40	<0.01	41	1.47	481	<1	131	2017	18	1.24	<5	<5	<10	246	3135	3	118	<10	13	31
146766D	1304594	0.006	<1	7.30	<2	520	2	13	1.32	<4	24	176	40	4.42	<0.01	40	1.47	487	<1	131	2006	14	1.19	5	<5	<10	244	3177	2	118	<10	13	31
146767	1304595	0.007	<1	6.05	<2	482	2	19	1.31	<4	22	166	37	4.26	0.05	39	1.50	476	<1	128	1899	15	1.11	<5	<5	<10	239	2726	9	103	<10	12	13
146768	1304596	0.009	<1	7.17	<2	504	3	6	1.41	<4	22	162	36	4.22	<0.01	42	1.54	459	<1	124	4466	15	1.26	<5	<5	<10	247	2947	<2	104	<10	13	11
146769	1304597	0.008	<1	6.64	<2	422	2	18	1.97	<4	20	155	34	3.93	<0.01	41	1.45	622	<1	100	2734	12	1.20	<5	<5	<10	295	2951	8	90	<10	13	22
146770	1304598	0.008	<1	7.15	<2	454	2	11	2.02	<4	20	157	25	3.35	<0.01	37	1.39	590	<1	105	2766	13	1.14	<5	<5	<10	284	2815	9	97	<10	13	16
146771	1304599	0.011	<1	7.46	<2	543	2	18	1.02	<4	27	169	49	4.77	<0.01	51	1.78	514	<1	114	2429	15	1.31	<5	<5	<10	201	3322	5	127	<10	12	22
146772	1304600	0.010	<1	4.96	<2	373	<2	13	2.50	<4	15	53	13	3.52	<0.01	12	1.46	693	<1	29	832	2	0.89	<5	<5	<10	300	2919	<2	121	19	17	13
146773	1304601	0.011	<1	6.62	<2	409	2	21	1.62	<4	21	152	36	3.96	<0.01	40	1.63	643	<1	97	3140	13	1.17	<5	<5	<10	254	2811	<2	99	<10	14	2
146774	1304602	0.010	<1	7.51	<2	471	3	14	1.31	<4	24	166	41	4.35	<0.01	50	1.73	615	<1	109	3161	16	1.23	<5	<5	<10	266	2975	8	113	<10	13	18
146775	1304603	0.010	<1	6.39	<2	358	2	15	1.44	<4	19	159	37	3.77	<0.01	43	1.42	577	<1	98	2044	18	1.32	<5	<5	<10	289	2512	2	85	<10	13	24

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, June 24, 2012

Certificate of Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 05/23/2012
 Date Completed: 06/06/2012
 Job #: 201241746
 Reference: TL 12 246
 Sample #: 319

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
146776	1304604	0.013	1	6.87	<2	360	2	4	1.80	<4	19	167	36	3.79	<0.01	43	1.46	635	<1	106	4311	15	1.54	<5	<5	<10	335	2550	6	87	<10	15	22
146777D	1304604	0.012	<1	6.61	<2	337	2	13	1.72	<4	19	157	34	3.58	<0.01	41	1.39	595	<1	101	2501	16	1.46	<5	<5	<10	320	2416	5	83	<10	15	21
146778	1304605	0.010	<1	6.10	<2	459	2	7	1.35	<4	21	159	36	4.02	<0.01	46	1.52	524	<1	97	2437	14	1.19	<5	<5	<10	282	2640	13	96	<10	11	33
146779	1304606	0.008	<1	5.70	<2	557	2	9	0.95	<4	20	150	24	3.95	<0.01	46	1.48	472	<1	102	3554	13	1.10	<5	<5	<10	250	2776	<2	97	<10	10	28
146780	1304607	0.011	<1	6.14	<2	578	2	16	0.92	<4	23	163	36	4.38	<0.01	50	1.62	514	<1	113	1346	14	1.19	<5	<5	<10	250	2724	<2	104	<10	11	35
146781	1304608	0.009	1	6.60	<2	536	2	6	1.18	<4	21	155	39	4.18	<0.01	52	1.56	547	<1	98	2807	19	1.27	<5	<5	<10	300	2774	5	97	<10	12	8
146782	1304609	0.012	1	6.57	<2	615	2	24	1.29	<4	23	161	37	4.23	<0.01	55	1.59	550	<1	102	2612	18	1.09	<5	<5	<10	330	2852	5	106	<10	12	30
146783	1304610	5.139	<1	4.17	373	1502	2	14	2.41	<4	12	115	71	3.44	<0.01	16	1.24	461	2	49	3985	20	1.91	33	<5	<10	201	1820	5	124	<10	15	173
146784	1304611	0.011	1	7.24	<2	500	2	25	1.58	<4	19	147	37	3.65	<0.01	53	1.45	533	<1	80	573	14	1.40	<5	<5	<10	365	2805	6	88	<10	12	20
146785	1304612	0.008	<1	5.98	<2	649	2	17	0.87	<4	24	166	38	4.44	<0.01	59	1.68	468	<1	117	2366	14	1.19	<5	<5	<10	251	2896	4	107	<10	11	29
146786	1304613	0.019	<1	5.39	<2	485	2	12	1.22	<4	19	141	30	3.46	<0.01	49	1.36	498	<1	88	2782	19	1.28	<5	<5	<10	314	2733	<2	85	<10	10	42
146787	1304614	0.009	<1	6.03	<2	513	2	18	1.33	<4	21	141	40	3.84	<0.01	55	1.45	516	<1	102	1831	16	1.44	<5	<5	<10	315	2830	<2	90	<10	11	48
146788D	1304614	0.010	2	5.73	<2	541	2	10	1.49	<4	21	159	39	3.85	<0.01	55	1.39	545	<1	96	1900	16	1.46	<5	<5	<10	356	2992	3	95	<10	10	42
146789	1304615	0.011	<1	6.03	<2	738	2	6	1.02	<4	24	177	35	4.43	0.05	62	1.59	532	<1	125	823	14	1.14	5	<5	<10	295	3296	11	115	<10	10	39
146790	1304616	0.008	<1	6.94	<2	747	2	5	1.18	<4	24	171	35	4.33	0.10	67	1.58	517	<1	115	1925	15	1.47	<5	<5	<10	313	3399	<2	114	<10	10	34
146791	1304617	0.011	<1	5.73	<2	593	2	14	1.51	<4	21	152	40	3.81	0.15	53	1.43	584	<1	97	4260	14	1.25	<5	<5	<10	339	3021	<2	97	<10	11	31
146792	1304618	0.009	1	5.74	<2	571	2	15	1.09	<4	20	153	34	3.79	0.09	51	1.45	442	<1	103	1899	17	1.31	<5	<5	<10	309	2860	3	92	<10	9	38
146793	1304619	0.009	<1	5.09	<2	496	2	8	1.19	<4	19	145	33	3.56	<0.01	49	1.34	544	<1	95	1900	15	1.13	<5	<5	<10	316	2847	8	87	<10	10	31
146794	1304620	0.011	<1	5.01	<2	394	2	17	2.69	<4	16	58	17	3.62	<0.01	16	1.46	737	<1	32	2910	<1	1.09	<5	<5	<10	320	3468	3	127	21	15	20
146795	1304621	0.008	<1	6.38	<2	690	2	5	1.61	<4	24	167	46	4.13	<0.01	59	1.50	597	<1	103	5207	16	1.38	<5	<5	<10	342	3433	4	102	<10	13	40

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, June 24, 2012

Certificate of Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 05/23/2012
 Date Completed: 06/06/2012
 Job #: 201241746
 Reference: TL 12 246
 Sample #: 319

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
146796	1304622	0.009	<1	5.33	<2	468	2	3	1.75	<4	6	32	6	1.66	<0.01	28	0.59	251	<1	50	3493	5	1.04	<5	<5	<10	442	1911	<2	37	<10	5	4
146797	1304623	0.009	<1	5.62	<2	476	2	1	1.91	<4	6	33	<1	1.70	<0.01	29	0.59	267	<1	52	2706	2	1.03	<5	<5	<10	646	1991	3	38	<10	5	4
146798	1304624	0.007	<1	4.41	<2	400	<2	<1	1.56	<4	5	24	<1	1.35	0.15	17	0.52	205	<1	41	3081	<1	0.83	<5	<5	<10	446	1540	<2	29	<10	6	<1
146799R	1304624	0.008	<1	4.97	<2	465	<2	<1	1.85	<4	6	31	<1	1.63	0.06	22	0.58	248	<1	55	2745	2	1.01	<5	<5	<10	502	1819	<2	34	<10	6	<1
146800	1304625	0.007	<1	5.75	<2	629	<2	<1	1.96	<4	6	29	7	1.69	<0.01	25	0.62	269	<1	46	2167	2	1.03	<5	<5	<10	554	1954	<2	36	<10	5	7
146801	1304626	<0.005	<1	5.78	<2	800	<2	5	1.83	<4	5	32	7	1.67	<0.01	26	0.63	263	<1	51	490	<1	0.92	<5	<5	<10	524	1974	<2	37	<10	5	6
146802	1304627	0.010	<1	5.26	<2	353	2	7	2.04	<4	6	31	<1	1.64	<0.01	24	0.58	259	<1	47	1541	2	0.95	<5	<5	<10	457	1835	<2	35	<10	5	6
146803	1304628	0.009	<1	5.33	<2	318	<2	7	2.06	<4	6	32	<1	1.61	<0.01	21	0.57	255	<1	48	1717	2	0.96	<5	<5	<10	519	1838	<2	35	<10	5	5
146804	1304629	0.008	<1	4.81	<2	416	2	3	2.10	<4	6	28	5	1.64	0.01	18	0.55	268	<1	44	2126	<1	0.80	<5	<5	<10	590	1797	<2	34	<10	5	2
146805	1304630	1.937	<1	4.42	<2	382	<2	4	2.38	<4	16	53	21	3.76	<0.01	16	1.39	711	<1	32	3460	2	1.06	<5	<5	<10	287	3144	6	124	21	14	20
146806	1304631	0.010	<1	4.98	<2	527	2	<1	2.00	<4	6	36	<1	1.71	<0.01	22	0.62	250	<1	51	2152	2	1.01	<5	<5	<10	498	1850	<2	39	<10	6	6
146807	1304632	0.009	<1	5.43	<2	563	2	7	1.92	<4	6	23	<1	1.58	<0.01	25	0.58	239	<1	34	3474	4	1.03	<5	<5	<10	333	1878	<2	35	<10	5	2
146808	1304633	0.009	<1	4.96	<2	536	<2	1	1.68	<4	6	20	<1	1.59	<0.01	22	0.61	254	<1	37	2569	6	1.11	<5	<5	<10	307	1796	3	35	<10	5	<1
146809	1304634	0.007	<1	5.19	<2	694	2	12	1.22	<4	16	138	22	3.17	<0.01	41	1.24	399	<1	100	2219	9	1.37	<5	<5	<10	301	2342	5	73	<10	11	11
146810D	1304634	0.008	<1	5.92	<2	645	2	9	1.12	<4	15	130	21	3.18	0.12	41	1.32	396	<1	92	3064	6	1.22	<5	<5	<10	265	2250	2	70	<10	13	10
146811	1304635	0.009	<1	5.21	<2	478	2	5	1.13	<4	17	135	26	3.28	0.13	38	1.24	430	<1	96	1456	14	1.35	<5	<5	<10	277	2582	<2	78	<10	10	16
146812	1304636	0.015	<1	4.82	<2	481	2	7	1.11	<4	17	147	25	3.28	<0.01	37	1.22	427	<1	110	<100	12	1.24	<5	<5	<10	261	2538	<2	79	<10	10	15
146813	1304637	0.011	<1	5.68	<2	471	2	5	1.42	<4	20	161	33	3.88	<0.01	43	1.44	574	<1	100	<100	14	1.11	<5	<5	<10	326	3037	<2	94	<10	12	25
146814	1304638	0.009	<1	5.67	<2	434	2	9	1.21	<4	20	149	24	3.70	<0.01	42	1.34	439	<1	98	3589	12	1.16	<5	<5	<10	282	2805	<2	92	<10	10	23
146815	1304639	0.010	<1	5.44	<2	468	2	9	1.64	<4	20	152	27	3.58	0.04	41	1.41	504	<1	94	962	12	1.12	<5	<5	<10	324	2946	3	90	<10	10	22

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, June 24, 2012


Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/23/2012
 Date Completed: 06/06/2012
 Job #: 201241746
 Reference: TL 12 246
 Sample #: 319

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
146816	1304640	0.013	<1	4.73	<2	364	2	4	2.52	<4	16	55	12	3.39	<0.01	16	1.37	686	<1	29	2863	<1	1.11	<5	<5	<10	302	3248	4	118	18	14	13
146817	1304641	0.012	<1	6.47	<2	541	3	<1	1.10	<4	26	185	30	4.88	0.08	49	1.72	540	<1	119	2702	21	1.07	<5	<5	<10	352	3407	<2	129	<10	11	28
146818	1304642	0.009	<1	6.15	61	635	2	<1	1.28	<4	24	172	50	4.51	<0.01	47	1.58	602	<1	109	3532	19	1.33	<5	<5	<10	328	3093	8	117	<10	10	32
146819	1304643	0.013	<1	5.96	<2	685	3	11	1.10	<4	25	188	38	4.52	<0.01	45	1.40	600	1	139	2130	15	1.26	<5	<5	<10	315	3352	<2	114	<10	10	35
146820	1304644	0.008	<1	4.78	9	516	2	5	1.54	<4	18	147	28	3.35	0.03	32	1.30	530	<1	94	1760	20	1.08	<5	<5	<10	332	2657	4	82	<10	11	16
146821D	1304644	0.008	<1	5.10	9	539	2	5	1.62	<4	19	151	30	3.43	<0.01	34	1.33	543	<1	94	1745	16	1.20	<5	<5	<10	342	2786	3	84	<10	11	14
146822	1304645	0.012	<1	4.59	<2	625	<2	17	0.94	<4	17	137	23	3.13	<0.01	26	1.19	456	<1	94	2451	13	0.97	<5	<5	<10	265	2428	3	77	<10	10	13
146823	1304646	0.013	<1	5.66	<2	631	2	5	1.80	<4	18	145	35	3.25	0.02	29	1.49	543	<1	111	2321	16	1.13	<5	<5	<10	369	2556	2	75	<10	12	17
146824	1304647	0.009	2	5.43	<2	642	2	4	1.23	<4	20	154	24	3.48	<0.01	31	1.28	501	<1	96	4114	26	1.13	<5	<5	<10	344	2873	<2	90	<10	9	23
146825	1304648	0.009	<1	5.12	<2	451	2	6	1.20	<4	18	153	29	3.31	<0.01	29	1.29	518	<1	101	2407	18	1.18	<5	<5	<10	303	2607	4	76	<10	9	21
146826	1304649	0.009	<1	5.57	<2	472	2	9	1.27	<4	16	139	27	3.18	<0.01	32	1.36	407	<1	85	2247	17	1.18	<5	<5	<10	299	2633	5	74	<10	9	18
146827	1304650	0.254	<1	1.31	163	>5000	<2	<1	1.02	<4	6	17	20	2.83	0.17	10	0.31	<100	5	12	1991	13	1.50	17	<5	<10	157	1171	<2	17	42	9	<1
146828	1304651	0.011	<1	4.69	<2	617	2	5	0.94	<4	17	165	32	3.54	0.12	26	1.36	330	1	146	3581	16	0.89	<5	<5	<10	261	2480	5	81	<10	12	21
146829	1304652	0.013	<1	5.58	<2	634	2	7	1.01	<4	19	148	22	3.82	<0.01	36	1.51	353	<1	114	3563	12	1.25	<5	<5	<10	302	2920	<2	92	<10	8	20
146830	1304653	0.010	<1	6.25	<2	518	2	6	1.21	<4	25	193	47	4.40	<0.01	36	1.52	567	2	158	2155	13	1.42	<5	<5	<10	314	3391	7	117	<10	11	16
146831	1304654	0.010	<1	5.73	<2	440	2	6	1.09	<4	24	182	43	4.32	<0.01	31	1.38	564	<1	132	3635	13	1.19	<5	<5	<10	292	3375	<2	115	<10	11	12
146832D	1304654	0.008	1	6.11	<2	444	2	<1	1.11	<4	24	178	42	4.30	<0.01	33	1.40	559	<1	119	3470	14	1.20	<5	<5	<10	293	3396	<2	115	<10	11	11
146833	1304655	0.011	<1	5.82	<2	557	2	5	1.30	<4	24	173	34	4.20	<0.01	30	1.51	625	<1	118	1646	13	1.17	<5	<5	<10	323	3231	4	110	<10	12	18
146834	1304656	0.009	<1	6.03	<2	452	2	5	1.15	<4	19	150	26	3.50	0.25	28	1.27	523	<1	123	1908	12	1.24	<5	<5	<10	279	2695	<2	90	<10	10	2
146835	1304657	0.009	<1	6.06	<2	693	2	<1	0.56	<4	21	145	33	4.15	0.12	32	1.69	360	<1	112	2217	11	1.05	<5	<5	<10	211	3107	<2	101	<10	9	25

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, June 24, 2012

Certificate of Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 05/23/2012
 Date Completed: 06/06/2012
 Job #: 201241746
 Reference: TL 12 246
 Sample #: 319

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
146836	1304658	0.007	<1	6.73	<2	936	2	19	0.67	<4	26	176	36	4.72	<0.01	36	1.70	431	<1	141	2325	13	1.19	<5	<5	<10	246	3475	<2	121	<10	7	32
146837	1304659	0.010	<1	6.32	<2	635	3	8	1.34	<4	25	155	63	4.57	<0.01	24	1.32	476	1	115	2614	17	1.65	<5	<5	<10	339	2919	<2	103	<10	10	29
146838	1304660	0.008	<1	5.16	<2	370	2	7	2.53	<4	16	54	12	3.38	<0.01	17	1.40	684	<1	29	4636	<1	1.12	<5	<5	<10	302	3289	3	118	23	15	11
146839	1304661	0.008	2	5.25	<2	545	2	8	1.13	<4	20	168	39	3.73	<0.01	25	1.27	459	<1	116	<100	13	1.22	<5	<5	<10	283	3038	2	93	<10	10	19
146840	1304662	0.006	<1	5.43	<2	586	2	10	1.41	<4	21	163	34	3.69	<0.01	26	1.35	538	<1	107	739	14	1.18	<5	<5	<10	330	3092	8	95	<10	11	22
146841	1304663	0.010	<1	5.20	<2	613	2	2	1.17	<4	23	178	45	4.16	<0.01	26	1.43	542	4	155	2180	15	1.08	<5	<5	<10	345	3204	2	104	<10	10	<1
146842	1304664	0.009	<1	4.97	<2	669	3	19	1.22	<4	19	174	27	3.64	<0.01	26	1.25	470	3	141	1447	17	1.16	<5	<5	<10	320	2948	6	90	<10	9	15
146843D	1304664	0.010	<1	6.07	<2	719	3	3	1.37	<4	21	185	28	3.87	<0.01	30	1.35	498	5	145	2292	20	1.23	<5	<5	<10	343	3122	<2	96	<10	10	18
146844	1304665	0.012	<1	5.21	<2	571	2	13	1.68	<4	21	166	36	3.77	0.12	26	1.42	543	<1	124	1064	17	1.24	<5	<5	<10	322	2912	<2	98	<10	11	25
146845	1304666	0.011	2	5.55	<2	543	2	<1	1.12	<4	23	162	33	4.20	<0.01	27	1.43	551	<1	117	2760	14	1.25	<5	<5	<10	280	3124	4	108	<10	10	24
146846	1304667	0.011	1	7.34	<2	469	2	<1	1.39	<4	22	167	38	4.00	<0.01	29	1.54	546	<1	114	1781	13	1.20	<5	<5	<10	307	2915	3	99	<10	13	23
146847	1304668	0.011	<1	5.82	<2	367	2	4	1.27	<4	22	185	49	4.15	0.12	28	1.49	488	<1	117	101	16	1.36	<5	<5	<10	258	2809	2	92	<10	11	31
146848	1304669	0.008	<1	5.60	<2	542	2	4	1.14	<4	23	175	42	4.01	<0.01	27	1.42	515	<1	126	587	13	1.07	<5	<5	<10	299	3142	4	105	<10	11	15
146849	1304670	5.298	<1	4.14	135	1497	2	11	2.41	<4	12	112	66	3.46	<0.01	18	1.20	459	2	47	2118	14	1.86	32	<5	<10	202	1971	5	123	<10	14	172
146850	1304671	0.012	<1	5.27	<2	587	2	<1	1.18	<4	23	171	41	4.06	<0.01	29	1.50	519	<1	117	3182	12	1.26	<5	<5	<10	298	3147	4	99	<10	11	5
146851	1304672	0.017	<1	7.13	<2	522	3	7	1.30	<4	24	168	38	4.19	<0.01	37	1.53	577	<1	118	2639	16	1.48	<5	<5	<10	328	3288	2	111	<10	10	19
146852	1304673	0.012	<1	5.93	<2	573	3	9	1.23	<4	25	185	35	4.48	<0.01	33	1.52	642	<1	133	1759	12	1.26	<5	<5	<10	334	3296	<2	114	<10	10	41
146853	1304674	0.011	<1	6.52	<2	699	2	9	1.30	<4	25	179	56	4.45	0.16	34	1.60	563	<1	121	1766	17	1.29	<5	<5	<10	377	3566	<2	118	<10	11	44
146854D	1304674	0.010	<1	6.23	<2	720	2	8	1.25	<4	26	185	34	4.60	<0.01	32	1.64	576	<1	114	1683	16	1.10	<5	<5	<10	385	3630	2	121	<10	11	38
146855	1304675	0.011	<1	5.36	<2	529	2	9	1.02	<4	22	157	39	4.09	<0.01	27	1.45	533	<1	105	2277	11	1.11	<5	<5	<10	268	3122	3	103	<10	10	31

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, June 24, 2012

Certificate of Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 05/23/2012
 Date Completed: 06/06/2012
 Job #: 201241746
 Reference: TL 12 246
 Sample #: 319

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
146856	1304676	0.013	<1	5.15	<2	539	2	<1	1.04	<4	24	157	38	4.19	<0.01	27	1.47	547	<1	99	1692	11	1.03	<5	<5	<10	280	3191	6	107	<10	10	31
146857	1304677	0.011	<1	4.92	<2	507	2	5	1.55	<4	21	158	37	3.86	<0.01	26	1.44	542	<1	96	1025	16	1.27	<5	<5	<10	319	3089	2	99	<10	10	27
146858	1304678	0.011	<1	4.68	<2	461	2	8	1.40	<4	21	167	35	3.73	<0.01	26	1.41	494	<1	96	3418	15	1.22	<5	<5	<10	286	2814	<2	87	<10	10	28
146859	1304679	0.011	<1	4.89	<2	423	2	5	1.45	<4	20	163	42	3.83	<0.01	30	1.38	531	<1	96	3203	11	1.26	<5	<5	<10	322	2424	2	88	<10	10	18
146860	1304680	0.011	<1	4.03	<2	333	<2	4	2.39	<4	16	52	12	3.32	<0.01	13	1.34	668	<1	29	3714	<1	1.02	<5	<5	<10	283	3071	<2	115	21	14	10
146861	1304681	0.012	<1	6.00	<2	658	2	2	1.03	<4	25	185	35	4.51	<0.01	33	1.63	596	<1	125	1983	13	1.27	<5	<5	<10	293	3275	3	116	<10	12	31
146862	1304682	0.013	<1	6.34	<2	666	3	15	1.13	<4	26	173	47	4.58	<0.01	30	1.55	616	<1	122	2025	12	1.23	<5	<5	<10	290	3239	7	119	<10	12	33
146863	1304683	0.012	<1	6.21	<2	482	3	21	1.53	<4	23	160	43	4.46	<0.01	33	1.71	598	<1	116	1820	14	1.22	<5	<5	<10	298	2792	3	98	<10	12	35
146864	1304684	0.011	<1	4.93	<2	490	2	9	1.19	<4	22	177	41	3.74	<0.01	26	1.25	517	<1	109	2296	17	1.28	<5	<5	<10	310	2788	<2	93	<10	10	23
146865R	1304684	0.011	<1	5.08	<2	547	3	6	1.25	<4	23	201	46	4.06	<0.01	27	1.28	558	2	135	2342	19	1.40	<5	<5	<10	323	3018	3	101	<10	10	30
146866	1304685	0.014	<1	5.37	<2	398	2	5	1.42	<4	20	160	35	3.66	0.05	27	1.33	493	<1	102	772	13	1.36	<5	<5	<10	306	2835	5	88	<10	11	28
146867	1304686	0.010	<1	4.37	<2	381	2	10	1.30	<4	18	152	28	3.37	<0.01	23	1.34	472	4	86	2968	13	1.18	<5	<5	<10	303	2746	8	81	<10	11	20
146868	1304687	0.011	<1	4.75	<2	473	2	9	1.36	<4	22	173	34	4.02	<0.01	24	1.33	584	<1	108	4543	12	1.13	<5	<5	<10	285	2967	7	95	<10	12	30
146869	1304688	0.011	2	4.93	<2	458	2	2	1.41	<4	19	146	31	3.76	<0.01	26	1.30	518	<1	82	2875	18	1.13	<5	<5	<10	292	2891	7	85	<10	11	23
146870	1304689	0.011	<1	5.06	<2	418	2	<1	1.32	<4	22	170	28	3.94	0.06	28	1.51	536	<1	113	1851	12	1.22	<5	<5	<10	343	3041	4	99	<10	11	28
146871	1304690	1.979	<1	4.22	<2	390	2	9	2.45	<4	17	56	23	3.94	<0.01	15	1.42	749	<1	32	1810	4	0.92	<5	<5	<10	291	3217	<2	130	22	14	23
146872	1304691	0.014	2	5.57	<2	623	2	<1	1.11	<4	25	189	46	4.44	<0.01	27	1.49	533	<1	104	3747	15	1.21	<5	<5	<10	305	3230	<2	112	<10	11	44
146873	1304692	0.011	<1	5.34	<2	521	2	8	1.21	<4	25	182	36	4.40	<0.01	26	1.49	559	<1	114	2664	14	1.01	<5	<5	<10	323	3104	<2	110	<10	11	35
146874	1304693	0.009	<1	5.59	<2	455	2	<1	1.37	<4	20	156	36	3.63	<0.01	29	1.26	484	<1	101	1816	12	1.39	<5	<5	<10	305	3018	<2	88	<10	10	23
146875	1304694	0.012	<1	5.32	<2	486	2	6	0.99	<4	19	130	29	3.43	0.04	28	1.22	451	<1	85	935	15	1.23	<5	<5	<10	256	2794	<2	88	<10	11	23

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, June 24, 2012


Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/23/2012
 Date Completed: 06/06/2012
 Job #: 201241746
 Reference: TL 12 246
 Sample #: 319

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
146876D	1304694	0.013	<1	5.72	<2	557	2	2	1.10	<4	23	155	34	3.90	0.04	30	1.35	511	<1	95	1061	16	1.23	<5	<5	<10	286	3194	3	101	<10	11	36
146877	1304695	0.017	<1	5.60	<2	539	2	7	1.05	<4	24	163	41	4.21	<0.01	33	1.47	591	<1	101	2383	13	1.11	<5	<5	<10	281	3283	5	108	<10	13	33
146878	1304696	0.018	<1	5.32	<2	513	2	16	1.09	<4	24	171	47	4.21	<0.01	32	1.41	572	<1	125	3032	12	1.19	<5	<5	<10	288	3254	7	107	<10	12	31
146879	1304697	0.013	<1	4.83	<2	375	2	<1	1.49	<4	21	180	40	3.71	<0.01	27	1.17	479	<1	91	1344	19	1.30	<5	<5	<10	338	3102	8	85	<10	13	25
146880	1304698	0.007	<1	4.82	<2	387	2	10	1.85	<4	24	200	49	4.25	0.11	28	1.32	562	<1	99	3598	19	1.42	<5	<5	<10	360	3301	<2	95	<10	13	30
146881	1304699	0.017	<1	4.34	<2	505	2	8	1.81	<4	23	159	39	3.92	<0.01	29	1.22	616	<1	94	5624	14	1.11	<5	<5	<10	333	3130	5	103	<10	13	33
146882	1304700	<0.005	2	3.77	<2	330	2	8	2.39	<4	15	53	12	3.31	<0.01	13	1.32	673	<1	30	2944	<1	0.89	<5	<5	<10	284	3092	5	116	18	14	10
146883	1304701	0.009	<1	4.61	<2	499	<2	<1	1.77	<4	8	53	5	2.00	<0.01	20	0.63	344	<1	53	1959	6	0.88	<5	<5	<10	368	2329	<2	44	<10	6	9
146884	1304702	0.011	<1	4.64	<2	551	<2	10	1.59	<4	7	44	<1	1.65	<0.01	19	0.48	258	<1	58	3067	5	0.81	<5	<5	<10	503	2328	<2	36	<10	5	2
146885	1304703	0.012	<1	4.52	<2	546	2	3	1.51	<4	5	38	<1	1.56	<0.01	16	0.49	255	<1	58	2784	1	0.72	<5	<5	<10	433	2058	<2	30	<10	4	2

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, June 6, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/23/2012
 Date Completed: 06/06/2012
 Job #: 201241746
 Reference: TL 12 246
 Sample #: 319

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
146536	1304385	14	<0.001	0.014
146537	1304386	12	<0.001	0.012
146538	1304387	6	<0.001	0.006
146539	1304388	11	<0.001	0.011
146540	1304389	12	<0.001	0.012
146541	1304390	1238	0.036	1.238
146542	1304391	10	<0.001	0.010
146543	1304392	5	<0.001	0.005
146544	1304393	<5	<0.001	<0.005
146545	1304394	<5	<0.001	<0.005
146546 Dup	1304394	<5	<0.001	<0.005
146547	1304395	10	<0.001	0.010
146548	1304396	6	<0.001	0.006
146549	1304397	13	<0.001	0.013
146550	1304398	45	0.001	0.045
146551	1304399	11	<0.001	0.011
146552	1304400	<5	<0.001	<0.005
146553	1304401	19	<0.001	0.019
146554	1304402	14	<0.001	0.014
146555	1304403	9	<0.001	0.009
146556	1304404	8	<0.001	0.008
146557 Dup	1304404	10	<0.001	0.010
146558	1304405	9	<0.001	0.009
146559	1304406	9	<0.001	0.009
146560	1304407	17	<0.001	0.017
146561	1304408	11	<0.001	0.011
146562	1304409	10	<0.001	0.010
146563	1304410	213	0.006	0.213
146564	1304411	11	<0.001	0.011
146565	1304412	19	<0.001	0.019

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Wednesday, June 6, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/23/2012
 Date Completed: 06/06/2012
 Job #: 201241746
 Reference: TL 12 246
 Sample #: 319

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
146566	1304413	10	<0.001	0.010
146567	1304414	7	<0.001	0.007
146568 Dup	1304414	8	<0.001	0.008
146569	1304415	10	<0.001	0.010
146570	1304416	9	<0.001	0.009
146571	1304417	6	<0.001	0.006
146572	1304418	8	<0.001	0.008
146573	1304419	10	<0.001	0.010
146574	1304420	5	<0.001	0.005
146575	1304421	10	<0.001	0.010
146576	1304422	12	<0.001	0.012
146577	1304423	9	<0.001	0.009
146578	1304424	6	<0.001	0.006
146579 Dup	1304424	9	<0.001	0.009
146580	1304425	8	<0.001	0.008
146581	1304426	10	<0.001	0.010
146582	1304427	116	0.003	0.116
146583	1304428	19	<0.001	0.019
146584	1304429	8	<0.001	0.008
146585	1304430	5261	0.153	5.261
146586	1304431	9	<0.001	0.009
146587	1304432	17	<0.001	0.017
146588	1304433	18	<0.001	0.018
146589	1304434	<5	<0.001	<0.005
146590 Dup	1304434	<5	<0.001	<0.005
146591	1304435	8	<0.001	0.008
146592	1304436	10	<0.001	0.010
146593	1304437	7	<0.001	0.007
146594	1304438	6	<0.001	0.006
146595	1304439	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Wednesday, June 6, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/23/2012
 Date Completed: 06/06/2012
 Job #: 201241746
 Reference: TL 12 246
 Sample #: 319

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
146596	1304440	<5	<0.001	<0.005
146597	1304441	153	0.004	0.153
146598	1304442	11	<0.001	0.011
146599	1304443	<5	<0.001	<0.005
146600	1304444	23	<0.001	0.023
146601 Rep	1304444	34	<0.001	0.034
146602	1304445	2798	0.082	2.798
146603	1304446	20	<0.001	0.020
146604	1304447	8	<0.001	0.008
146605	1304448	18	<0.001	0.018
146606	1304449	16	<0.001	0.016
146607	1304450	2091	0.061	2.091
146608	1304451	17	<0.001	0.017
146609	1304452	103	0.003	0.103
146610	1304453	42	0.001	0.042
146611	1304454	10	<0.001	0.010
146612 Dup	1304454	10	<0.001	0.010
146613	1304455	7	<0.001	0.007
146614	1304456	17	<0.001	0.017
146615	1304457	11	<0.001	0.011
146616	1304458	<5	<0.001	<0.005
146617	1304459	<5	<0.001	<0.005
146618	1304460	7	<0.001	0.007
146619	1304461	7	<0.001	0.007
146620	1304462	12	<0.001	0.012
146621	1304463	39	0.001	0.039
146622	1304464	30	<0.001	0.030
146623 Dup	1304464	41	0.001	0.041
146624	1304465	20	<0.001	0.020
146625	1304466	6	<0.001	0.006

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Wednesday, June 6, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/23/2012
 Date Completed: 06/06/2012
 Job #: 201241746
 Reference: TL 12 246
 Sample #: 319

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
146626	1304467	6	<0.001	0.006
146627	1304468	<5	<0.001	<0.005
146628	1304469	<5	<0.001	<0.005
146629	1304470	282	0.008	0.282
146630	1304471	<5	<0.001	<0.005
146631	1304472	<5	<0.001	<0.005
146632	1304473	<5	<0.001	<0.005
146633	1304474	<5	<0.001	<0.005
146634 Dup	1304474	<5	<0.001	<0.005
146635	1304475	<5	<0.001	<0.005
146636	1304476	<5	<0.001	<0.005
146637	1304477	<5	<0.001	<0.005
146638	1304478	<5	<0.001	<0.005
146639	1304479	<5	<0.001	<0.005
146640	1304480	<5	<0.001	<0.005
146641	1304481	<5	<0.001	<0.005
146642	1304482	<5	<0.001	<0.005
146643	1304483	<5	<0.001	<0.005
146644	1304484	<5	<0.001	<0.005
146645 Dup	1304484	<5	<0.001	<0.005
146646	1304485	<5	<0.001	<0.005
146647	1304486	<5	<0.001	<0.005
146648	1304487	<5	<0.001	<0.005
146649	1304488	5	<0.001	0.005
146650	1304489	<5	<0.001	<0.005
146651	1304490	5134	0.150	5.134
146652	1304491	<5	<0.001	<0.005
146653	1304492	5	<0.001	0.005
146654	1304493	<5	<0.001	<0.005
146655	1304494	5	<0.001	0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Wednesday, June 6, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/23/2012
 Date Completed: 06/06/2012
 Job #: 201241746
 Reference: TL 12 246
 Sample #: 319

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
146656 Dup	1304494	5	<0.001	0.005
146657	1304495	5	<0.001	0.005
146658	1304496	<5	<0.001	<0.005
146659	1304497	6	<0.001	0.006
146660	1304498	<5	<0.001	<0.005
146661	1304499	<5	<0.001	<0.005
146662	1304500	<5	<0.001	<0.005
146663	1304501	<5	<0.001	<0.005
146664	1304502	5	<0.001	0.005
146665	1304503	<5	<0.001	<0.005
146666	1304504	6	<0.001	0.006
146667 Rep	1304504	<5	<0.001	<0.005
146668	1304505	<5	<0.001	<0.005
146669	1304506	6	<0.001	0.006
146670	1304507	5	<0.001	0.005
146671	1304508	<5	<0.001	<0.005
146672	1304509	<5	<0.001	<0.005
146673	1304510	2040	0.060	2.040
146674	1304511	12	<0.001	0.012
146675	1304512	<5	<0.001	<0.005
146676	1304513	7	<0.001	0.007
146677	1304514	5	<0.001	0.005
146678 Dup	1304514	<5	<0.001	<0.005
146679	1304515	5	<0.001	0.005
146680	1304516	7	<0.001	0.007
146681	1304517	<5	<0.001	<0.005
146682	1304518	<5	<0.001	<0.005
146683	1304519	<5	<0.001	<0.005
146684	1304520	<5	<0.001	<0.005
146685	1304521	6	<0.001	0.006

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Wednesday, June 6, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/23/2012
 Date Completed: 06/06/2012
 Job #: 201241746
 Reference: TL 12 246
 Sample #: 319

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
146686	1304522	8	<0.001	0.008
146687	1304523	6	<0.001	0.006
146688	1304524	8	<0.001	0.008
146689 Dup	1304524	7	<0.001	0.007
146690	1304525	5	<0.001	0.005
146691	1304526	6	<0.001	0.006
146692	1304527	7	<0.001	0.007
146693	1304528	7	<0.001	0.007
146694	1304529	5	<0.001	0.005
146695	1304530	229	0.007	0.229
146696	1304531	6	<0.001	0.006
146697	1304532	<5	<0.001	<0.005
146698	1304533	6	<0.001	0.006
146699	1304534	7	<0.001	0.007
146700 Dup	1304534	7	<0.001	0.007
146701	1304535	6	<0.001	0.006
146702	1304536	<5	<0.001	<0.005
146703	1304537	6	<0.001	0.006
146704	1304538	6	<0.001	0.006
146705	1304539	5	<0.001	0.005
146706	1304540	8	<0.001	0.008
146707	1304541	<5	<0.001	<0.005
146708	1304542	<5	<0.001	<0.005
146709	1304543	6	<0.001	0.006
146710	1304544	<5	<0.001	<0.005
146711 Dup	1304544	<5	<0.001	<0.005
146712	1304545	<5	<0.001	<0.005
146713	1304546	5	<0.001	0.005
146714	1304547	<5	<0.001	<0.005
146715	1304548	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Wednesday, June 6, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/23/2012
 Date Completed: 06/06/2012
 Job #: 201241746
 Reference: TL 12 246
 Sample #: 319

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
146716	1304549	<5	<0.001	<0.005
146717	1304550	5315	0.155	5.315
146718	1304551	6	<0.001	0.006
146719	1304552	5	<0.001	0.005
146720	1304553	6	<0.001	0.006
146721	1304554	8	<0.001	0.008
146722 Dup	1304554	9	<0.001	0.009
146723	1304555	8	<0.001	0.008
146724	1304556	5	<0.001	0.005
146725	1304557	7	<0.001	0.007
146726	1304558	8	<0.001	0.008
146727	1304559	5	<0.001	0.005
146728	1304560	<5	<0.001	<0.005
146729	1304561	8	<0.001	0.008
146730	1304562	<5	<0.001	<0.005
146731	1304563	8	<0.001	0.008
146732	1304564	5	<0.001	0.005
146733 Rep	1304564	7	<0.001	0.007
146734	1304565	8	<0.001	0.008
146735	1304566	8	<0.001	0.008
146736	1304567	6	<0.001	0.006
146737	1304568	5	<0.001	0.005
146738	1304569	7	<0.001	0.007
146739	1304570	1905	0.056	1.905
146740	1304571	10	<0.001	0.010
146741	1304572	6	<0.001	0.006
146742	1304573	8	<0.001	0.008
146743	1304574	7	<0.001	0.007
146744 Dup	1304574	5	<0.001	0.005
146745	1304575	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Wednesday, June 6, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/23/2012
 Date Completed: 06/06/2012
 Job #: 201241746
 Reference: TL 12 246
 Sample #: 319

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
146746	1304576	<5	<0.001	<0.005
146747	1304577	<5	<0.001	<0.005
146748	1304578	<5	<0.001	<0.005
146749	1304579	6	<0.001	0.006
146750	1304580	<5	<0.001	<0.005
146751	1304581	<5	<0.001	<0.005
146752	1304582	5	<0.001	0.005
146753	1304583	<5	<0.001	<0.005
146754	1304584	<5	<0.001	<0.005
146755 Dup	1304584	5	<0.001	0.005
146756	1304585	8	<0.001	0.008
146757	1304586	<5	<0.001	<0.005
146758	1304587	5	<0.001	0.005
146759	1304588	6	<0.001	0.006
146760	1304589	<5	<0.001	<0.005
146761	1304590	252	0.007	0.252
146762	1304591	6	<0.001	0.006
146763	1304592	5	<0.001	0.005
146764	1304593	<5	<0.001	<0.005
146765	1304594	6	<0.001	0.006
146766 Dup	1304594	6	<0.001	0.006
146767	1304595	7	<0.001	0.007
146768	1304596	9	<0.001	0.009
146769	1304597	8	<0.001	0.008
146770	1304598	8	<0.001	0.008
146771	1304599	11	<0.001	0.011
146772	1304600	10	<0.001	0.010
146773	1304601	11	<0.001	0.011
146774	1304602	10	<0.001	0.010
146775	1304603	10	<0.001	0.010

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Wednesday, June 6, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/23/2012
 Date Completed: 06/06/2012
 Job #: 201241746
 Reference: TL 12 246
 Sample #: 319

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
146776	1304604	13	<0.001	0.013
146777 Dup	1304604	12	<0.001	0.012
146778	1304605	10	<0.001	0.010
146779	1304606	8	<0.001	0.008
146780	1304607	11	<0.001	0.011
146781	1304608	9	<0.001	0.009
146782	1304609	12	<0.001	0.012
146783	1304610	5139	0.150	5.139
146784	1304611	11	<0.001	0.011
146785	1304612	8	<0.001	0.008
146786	1304613	19	<0.001	0.019
146787	1304614	9	<0.001	0.009
146788 Dup	1304614	10	<0.001	0.010
146789	1304615	11	<0.001	0.011
146790	1304616	8	<0.001	0.008
146791	1304617	11	<0.001	0.011
146792	1304618	9	<0.001	0.009
146793	1304619	9	<0.001	0.009
146794	1304620	11	<0.001	0.011
146795	1304621	8	<0.001	0.008
146796	1304622	9	<0.001	0.009
146797	1304623	9	<0.001	0.009
146798	1304624	7	<0.001	0.007
146799 Rep	1304624	8	<0.001	0.008
146800	1304625	7	<0.001	0.007
146801	1304626	<5	<0.001	<0.005
146802	1304627	10	<0.001	0.010
146803	1304628	9	<0.001	0.009
146804	1304629	8	<0.001	0.008
146805	1304630	1937	0.057	1.937

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Wednesday, June 6, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/23/2012
 Date Completed: 06/06/2012
 Job #: 201241746
 Reference: TL 12 246
 Sample #: 319

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
146806	1304631	10	<0.001	0.010
146807	1304632	9	<0.001	0.009
146808	1304633	9	<0.001	0.009
146809	1304634	7	<0.001	0.007
146810 Dup	1304634	8	<0.001	0.008
146811	1304635	9	<0.001	0.009
146812	1304636	15	<0.001	0.015
146813	1304637	11	<0.001	0.011
146814	1304638	9	<0.001	0.009
146815	1304639	10	<0.001	0.010
146816	1304640	13	<0.001	0.013
146817	1304641	12	<0.001	0.012
146818	1304642	9	<0.001	0.009
146819	1304643	13	<0.001	0.013
146820	1304644	8	<0.001	0.008
146821 Dup	1304644	8	<0.001	0.008
146822	1304645	12	<0.001	0.012
146823	1304646	13	<0.001	0.013
146824	1304647	9	<0.001	0.009
146825	1304648	9	<0.001	0.009
146826	1304649	9	<0.001	0.009
146827	1304650	254	0.007	0.254
146828	1304651	11	<0.001	0.011
146829	1304652	13	<0.001	0.013
146830	1304653	10	<0.001	0.010
146831	1304654	10	<0.001	0.010
146832 Dup	1304654	8	<0.001	0.008
146833	1304655	11	<0.001	0.011
146834	1304656	9	<0.001	0.009
146835	1304657	9	<0.001	0.009

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Wednesday, June 6, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/23/2012
 Date Completed: 06/06/2012
 Job #: 201241746
 Reference: TL 12 246
 Sample #: 319

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
146836	1304658	7	<0.001	0.007
146837	1304659	10	<0.001	0.010
146838	1304660	8	<0.001	0.008
146839	1304661	8	<0.001	0.008
146840	1304662	6	<0.001	0.006
146841	1304663	10	<0.001	0.010
146842	1304664	9	<0.001	0.009
146843 Dup	1304664	10	<0.001	0.010
146844	1304665	12	<0.001	0.012
146845	1304666	11	<0.001	0.011
146846	1304667	11	<0.001	0.011
146847	1304668	11	<0.001	0.011
146848	1304669	8	<0.001	0.008
146849	1304670	5298	0.155	5.298
146850	1304671	12	<0.001	0.012
146851	1304672	17	<0.001	0.017
146852	1304673	12	<0.001	0.012
146853	1304674	11	<0.001	0.011
146854 Dup	1304674	10	<0.001	0.010
146855	1304675	11	<0.001	0.011
146856	1304676	13	<0.001	0.013
146857	1304677	11	<0.001	0.011
146858	1304678	11	<0.001	0.011
146859	1304679	11	<0.001	0.011
146860	1304680	11	<0.001	0.011
146861	1304681	12	<0.001	0.012
146862	1304682	13	<0.001	0.013
146863	1304683	12	<0.001	0.012
146864	1304684	11	<0.001	0.011
146865 Rep	1304684	11	<0.001	0.011

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Wednesday, June 6, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 05/23/2012
 Date Completed: 06/06/2012
 Job #: 201241746
 Reference: TL 12 246
 Sample #: 319

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
146866	1304685	14	<0.001	0.014
146867	1304686	10	<0.001	0.010
146868	1304687	11	<0.001	0.011
146869	1304688	11	<0.001	0.011
146870	1304689	11	<0.001	0.011
146871	1304690	1979	0.058	1.979
146872	1304691	14	<0.001	0.014
146873	1304692	11	<0.001	0.011
146874	1304693	9	<0.001	0.009
146875	1304694	12	<0.001	0.012
146876 Dup	1304694	13	<0.001	0.013
146877	1304695	17	<0.001	0.017
146878	1304696	18	<0.001	0.018
146879	1304697	13	<0.001	0.013
146880	1304698	7	<0.001	0.007
146881	1304699	17	<0.001	0.017
146882	1304700	<5	<0.001	<0.005
146883	1304701	9	<0.001	0.009
146884	1304702	11	<0.001	0.011
146885	1304703	12	<0.001	0.012

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianiuk H. B.Sc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, May 22, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/24/2012
 Date Completed: 05/03/2012
 Job #: 201241307
 Reference: TL 12 247
 Sample #: 132

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm	
111478	1304077	0.035	<1	4.27	12	500	4	3	1.42	<4	6	22	11	1.42	0.60	13	0.83	400	3	39	388	19	0.45	<5	21	<10	126	1780	<2	28	<10	4	86	
111479	1304078	0.152	1	3.39	23	449	3	16	1.04	<4	4	31	46	1.50	0.32	7	0.71	459	5	51	317	18	1.01	<5	14	<10	88	1454	2	25	<10	3	44	
111480	1304079	0.522	4	4.59	32	471	3	20	2.22	<4	4	28	241	2.93	0.44	9	1.21	757	4	48	287	16	2.60	<5	17	<10	111	1285	<2	23	<10	5	57	
111481	1304080	<0.005	<1	3.88	3	435	3	21	2.21	<4	14	51	26	3.29	0.13	8	1.22	676	<1	37	580	9	0.13	<5	13	<10	262	2985	<2	108	21	12	58	
111482	1304081	0.162	1	4.02	21	489	3	3	1.77	<4	5	33	49	1.84	0.30	11	0.94	554	5	51	321	14	1.12	<5	11	<10	132	1514	<2	27	<10	4	45	
111483	1304082	0.201	2	5.88	37	483	3	32	2.94	<4	21	143	84	3.67	0.48	16	1.43	776	7	115	435	16	2.09	<5	14	<10	151	2580	2	80	<10	13	436	
111484	1304083	7.916	2	4.52	8	319	3	15	1.47	4	16	158	92	3.19	0.34	19	1.29	515	7	110	505	12	1.03	<5	5	<10	121	2806	<2	90	11	8	858	
111485	1304084	0.090	1	5.30	4	352	3	23	1.61	<4	17	152	62	3.51	0.51	24	1.69	680	6	101	499	13	0.56	<5	15	<10	138	2832	3	79	<10	11	236	
111486	1304085	0.016	<1	4.48	4	345	3	18	1.52	<4	17	153	40	3.29	0.26	25	1.55	594	11	100	495	14	0.30	<5	16	<10	133	2812	2	79	<10	9	73	
111487	1304086	0.034	1	3.96	4	361	3	31	1.28	<4	24	135	52	3.92	0.19	20	1.15	410	6	105	448	18	1.22	<5	20	<10	124	2517	<2	66	<10	8	60	
111488D	1304086	0.031	1	4.38	5	351	3	21	1.37	<4	24	134	55	4.16	0.44	20	1.23	421	6	106	470	18	1.35	<5	12	<10	129	2413	<2	63	<10	10	64	
111489	1304087	0.015	<1	5.03	12	400	3	20	2.07	<4	21	140	63	3.71	0.73	24	1.12	425	5	87	490	17	1.14	<5	10	<10	161	2538	4	71	<10	11	149	
111490	1304088	0.022	<1	4.07	6	337	3	26	1.19	<4	18	130	42	3.21	0.40	15	0.98	300	4	87	454	21	1.22	<5	12	<10	139	2591	<2	73	<10	7	76	
111491	1304089	0.014	1	5.26	23	355	3	20	1.81	<4	17	131	40	3.12	0.26	19	1.34	359	4	81	510	18	0.72	<5	14	<10	172	2506	<2	67	<10	11	107	
111492	1304090																																	
111493	1304091	0.012	<1	4.93	8	529	2	23	2.75	<4	12	83	39	2.99	0.26	14	1.22	620	6	80	379	15	0.77	<5	12	<10	234	1856	3	47	<10	7	79	
111494	1304092	0.030	1	3.87	6	305	3	27	2.16	<4	24	140	99	7.41	0.27	15	0.84	418	6	119	312	20	2.35	<5	<5	<10	196	1757	<2	46	<10	6	251	
111495	1304093	0.008	<1	4.33	17	272	3	11	1.93	<4	11	36	60	3.34	0.25	12	0.52	339	2	56	333	16	0.78	<5	16	<10	197	1517	<2	31	<10	4	120	
111496	1304094	<0.005	<1	4.18	7	356	3	29	1.94	<4	5	26	50	1.49	0.22	12	0.95	521	4	43	319	16	0.91	<5	7	<10	230	1169	5	24	<10	3	45	
111497	1304095	0.150	1	5.15	14	218	3	32	2.28	4	12	47	94	6.93	0.50	14	1.69	886	4	79	324	22	5.45	7	11	<10	161	1072	<2	38	11	6	657	

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, May 22, 2012

Certificate of Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 04/24/2012
 Date Completed: 05/03/2012
 Job #: 201241307
 Reference: TL 12 247
 Sample #: 132

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
111498	1304096	0.056	2	4.78	17	193	3	20	2.19	5	13	41	90	7.31	0.54	13	1.61	827	3	70	323	27	5.84	<5	8	<10	161	981	<2	36	<10	6	648
111499D	1304096	0.052	2	5.12	12	194	3	13	2.18	4	13	44	88	7.25	0.49	16	1.56	817	5	76	323	23	5.73	<5	10	<10	163	984	2	35	<10	6	628
111500	1304097	0.070	2	2.40	10	136	4	33	0.93	<4	33	41	103	8.41	0.68	9	0.71	510	2	75	198	25	7.00	<5	<5	<10	114	597	<2	20	<10	4	245
111501	1304098	0.013	<1	3.83	5	362	3	13	1.67	<4	7	29	23	2.65	0.50	13	0.88	602	1	39	415	24	2.10	<5	10	<10	168	1090	6	32	<10	4	114
111502	1304099	0.104	4	3.57	15	115	5	42	1.23	9	48	56	200	16.55	0.02	10	0.83	532	8	135	226	65	>10.00	5	18	<10	98	663	<2	40	11	5	1064
111503	1304100	<0.005	<1	5.89	5	354	3	26	2.40	<4	16	55	27	3.79	0.20	11	1.41	705	<1	38	626	9	0.37	<5	15	<10	278	2948	11	113	22	15	84
111504	1304101	0.120	4	3.41	3	151	5	37	0.81	10	67	56	245	16.41	<0.01	9	0.76	425	5	132	241	68	>10.00	<5	<5	<10	94	816	2	45	16	5	1620
111505	1304102	0.191	4	3.63	2	60	4	32	0.95	7	68	41	184	16.51	0.29	18	1.80	6497	1	92	182	69	>10.00	<5	<5	10	93	1206	8	44	<10	11	809
111506	1304103	0.042	<1	6.20	7	115	3	33	3.60	<4	58	44	73	7.92	0.30	39	2.17	3761	<1	72	859	39	2.01	<5	<5	<10	228	6069	9	317	<10	32	229
111507	1304104	0.038	<1	5.08	5	3	3	38	4.59	5	46	43	66	12.56	0.35	30	2.39	2927	<1	75	749	37	2.17	5	<5	<10	145	4393	10	283	<10	33	204
111508	1304105	0.107	1	5.47	6	30	3	40	4.08	17	44	47	78	12.23	0.48	40	2.53	2688	<1	84	655	42	4.01	<5	<5	<10	135	5141	<2	277	18	33	1919
111509	1304106	0.049	<1	5.87	3	140	3	46	5.49	4	56	48	92	9.49	0.41	47	2.61	2166	<1	80	786	27	3.40	<5	<5	<10	166	7428	8	299	<10	34	246
111510D	1304106	0.034	<1	5.43	4	135	3	30	5.24	<4	54	44	89	9.00	0.48	46	2.50	2021	<1	74	766	21	3.33	5	5	<10	159	7028	11	286	<10	33	204
111511	1304107	0.020	<1	6.50	4	141	4	29	3.96	5	48	53	77	9.14	0.51	58	2.03	1679	<1	76	932	30	2.71	<5	<5	<10	161	6512	9	290	<10	36	458
111512	1304108	0.038	1	3.77	<2	114	4	27	5.59	4	78	52	128	12.20	0.71	40	2.47	2143	<1	80	562	55	6.33	<5	<5	<10	140	4972	11	235	<10	24	292
111513	1304109	0.006	<1	5.49	<2	38	4	37	5.32	<4	50	65	84	9.09	0.76	34	2.50	2155	<1	73	718	29	1.26	<5	<5	<10	161	5764	3	285	<10	31	147
111514	1304110	0.224	<1	1.82	402	1562	2	15	1.07	<4	7	19	31	3.06	0.57	8	0.33	124	10	15	101	19	0.78	19	9	<10	85	1122	<2	22	52	9	28
111515	1304111	0.010	<1	4.85	6	27	3	33	5.66	4	56	74	71	10.06	0.27	21	2.08	2554	<1	80	782	22	1.46	<5	<5	<10	269	8135	<2	325	<10	30	140
111516	1304112	0.038	<1	5.08	<2	26	4	25	4.81	<4	45	49	91	9.66	0.17	26	2.36	2122	<1	57	715	26	2.56	<5	<5	<10	181	5531	7	250	<10	31	137
111517	1304113	0.024	1	4.96	<2	28	4	39	5.07	4	43	44	157	12.65	0.15	30	2.32	2908	<1	63	698	29	3.25	5	<5	<10	174	4872	<2	272	<10	35	158

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, May 22, 2012

Certificate of Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 04/24/2012
 Date Completed: 05/03/2012
 Job #: 201241307
 Reference: TL 12 247
 Sample #: 132

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
111518	1304114	0.039	<1	5.48	<2	16	3	38	5.61	4	47	57	68	9.91	0.25	31	2.15	2443	<1	68	834	23	1.00	<5	<5	<10	191	5674	<2	288	<10	35	156
111519	1304115	0.013	<1	5.38	<2	<1	4	49	4.73	4	47	60	86	9.96	0.18	32	2.12	1938	<1	72	739	23	1.49	<5	<5	<10	154	4737	<2	264	<10	31	183
111520	1304116	0.018	<1	5.57	<2	<1	3	57	5.00	<4	48	60	83	10.27	0.51	31	2.17	2047	<1	72	740	25	1.47	<5	<5	<10	165	5240	8	277	<10	32	198
111521D	1304116	0.018	<1	4.88	2	<1	3	35	5.00	4	49	58	84	10.38	0.48	31	2.19	2050	<1	69	742	23	1.49	7	<5	<10	161	4996	4	280	<10	32	194
111522	1304117	0.114	1	3.00	3	39	4	29	3.79	6	230	47	269	17.99	0.45	23	1.48	2460	<1	82	548	43	>10.00	5	<5	<10	126	4246	<2	223	<10	23	155
111523	1304118	0.027	1	4.82	<2	<1	3	25	4.94	<4	54	58	108	9.10	0.27	27	2.00	1383	<1	69	775	21	1.91	<5	<5	<10	196	5045	<2	271	<10	35	121
111524	1304119	0.025	<1	4.51	2	70	3	37	4.46	<4	46	53	81	8.63	0.48	28	1.77	1485	<1	65	764	20	1.53	<5	<5	<10	158	4720	7	268	<10	31	172
111525	1304120	0.006	<1	3.89	6	261	3	16	2.06	<4	15	47	21	3.24	0.22	10	1.37	623	<1	30	580	5	0.12	<5	13	<10	205	2383	2	101	21	15	58
111526	1304121	0.030	<1	5.38	<2	15	4	16	5.11	<4	49	64	73	9.42	0.26	30	2.09	1754	<1	74	715	20	1.00	<5	<5	<10	176	5167	<2	279	<10	31	134
111527	1304122	0.019	1	5.41	2	56	3	20	5.61	4	50	69	199	11.68	0.33	34	2.27	2150	<1	75	749	25	3.03	<5	<5	<10	201	4841	<2	280	<10	35	165
111528	1304123	0.012	<1	5.87	2	<1	3	33	5.36	<4	52	71	107	9.28	0.59	33	2.36	1483	<1	76	770	18	1.09	6	<5	<10	203	5897	2	294	<10	34	129
111529	1304124	0.017	1	6.60	7	37	3	39	5.58	<4	49	69	83	9.32	0.55	38	2.42	1826	<1	70	812	27	1.74	<5	<5	11	248	6119	5	318	<10	37	148
111530	1304125	0.248	2	5.28	10	38	4	29	4.99	4	69	66	98	12.27	0.62	32	2.23	1461	<1	77	611	27	6.08	5	<5	<10	172	4919	<2	249	14	31	133
111531	1304126	0.038	19	3.43	14	15	4	43	2.42	9	154	41	195	22.63	0.52	22	1.18	1155	1	96	211	59	>10.00	5	<5	<10	87	1996	9	96	<10	14	152
111532D	1304126	0.051	47	2.41	17	8	5	39	2.17	8	151	40	193	22.20	0.27	19	1.08	1113	<1	89	196	63	>10.00	<5	<5	<10	80	1864	7	92	<10	13	151
111533	1304127	0.027	2	5.66	12	28	3	22	5.21	<4	50	60	46	8.84	0.60	31	2.06	1595	<1	70	767	33	2.81	5	5	<10	158	5306	10	274	<10	35	137
111534	1304128	0.050	2	2.38	6	136	4	28	6.64	<4	47	49	64	9.99	0.56	38	2.50	2025	<1	59	573	25	5.24	<5	<5	<10	163	6583	<2	224	<10	23	108
111535	1304129	0.059	1	4.53	4	54	3	35	3.75	<4	35	62	106	9.46	0.54	43	2.19	1614	<1	63	599	38	4.28	<5	<5	<10	119	4822	<2	234	<10	28	168
111536	1304130	3.522	<1	3.95	371	1006	3	10	2.27	<4	12	110	75	3.36	0.56	14	1.17	478	11	52	769	26	1.21	34	17	<10	173	1727	<2	115	<10	13	211
111537	1304131	0.028	<1	5.81	8	54	3	13	4.56	<4	46	67	88	9.07	0.61	48	2.48	1375	<1	61	810	24	1.08	7	<5	<10	156	4088	3	302	<10	35	129

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, May 22, 2012


Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/24/2012
 Date Completed: 05/03/2012
 Job #: 201241307
 Reference: TL 12 247
 Sample #: 132

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
111538	1304132	0.059	<1	5.31	4	63	3	36	5.42	<4	46	52	103	8.41	0.84	34	2.43	1618	<1	59	745	19	2.03	5	<5	<10	169	5381	4	294	<10	30	107
111539	1304133	0.026	<1	5.34	4	43	3	22	4.59	<4	50	56	95	8.72	0.86	26	1.88	1528	<1	63	828	18	1.24	<5	<5	<10	150	6316	23	313	<10	32	120
111540	1304134	0.018	<1	5.14	<2	9	3	16	5.39	<4	47	57	97	9.92	0.57	28	2.25	1710	<1	64	781	21	1.39	<5	<5	<10	185	5374	4	282	<10	32	124
111541	1304135	0.029	1	5.92	2	11	3	11	6.15	4	55	71	113	10.31	0.80	29	2.45	1798	<1	77	754	25	1.68	<5	<5	<10	214	6059	11	292	<10	33	128
111542	1304136	0.036	<1	>10.00	6	72	2	33	>10.00	4	56	145	114	9.41	2.29	70	2.34	1515	2	68	696	18	1.63	<5	15	<10	182	4598	6	273	10	33	128
111543R	1304136	0.031	<1	>10.00	10	78	<2	43	>10.00	<4	57	152	114	9.92	2.36	74	2.49	1611	4	76	692	20	1.69	<5	19	<10	198	4829	6	286	<10	34	127
111544	1304137	0.018	<1	>10.00	11	133	<2	40	>10.00	4	51	158	93	9.26	2.84	80	2.52	1538	2	78	682	18	1.10	5	31	<10	189	4748	16	296	<10	33	126
111545	1304138	0.031	3	9.90	9	60	<2	44	5.84	8	53	119	268	21.58	2.48	71	1.74	1736	4	133	284	52	>10.00	6	16	<10	100	2067	21	166	<10	20	112
111546	1304139	0.048	2	>10.00	11	89	<2	49	9.07	4	55	162	67	10.48	2.82	99	2.52	1649	7	84	611	32	3.21	<5	23	<10	143	3680	20	276	<10	31	149
111547	1304140	0.006	<1	>10.00	13	723	<2	27	4.91	<4	13	110	20	3.07	2.34	37	1.29	595	2	27	550	8	0.10	<5	35	<10	256	2476	4	101	15	16	49
111548	1304141	0.025	3	>10.00	9	125	<2	49	>10.00	4	42	145	58	10.11	2.46	101	2.33	2110	5	63	618	26	1.41	<5	20	<10	165	4727	14	275	10	33	186
111549	1304142	0.023	1	>10.00	11	246	<2	31	>10.00	<4	47	110	73	8.62	2.50	75	3.21	2406	<1	54	611	26	2.00	<5	26	<10	208	6036	16	246	<10	29	137
111550	1304143	0.036	1	>10.00	7	421	<2	47	>10.00	<4	44	129	64	8.95	2.38	92	3.49	2553	<1	54	579	30	2.49	5	24	<10	250	7216	15	246	<10	30	131
111551	1304144	0.025	1	>10.00	2	388	<2	26	8.74	<4	42	139	52	8.14	2.35	91	2.47	1956	3	65	604	23	1.54	<5	28	<10	246	5928	7	253	10	28	135
111552	1304145	0.043	1	>10.00	9	619	<2	30	8.13	<4	47	136	90	9.29	2.55	81	2.32	2157	1	65	607	36	2.71	<5	26	<10	322	7351	25	268	<10	32	160
111553	1304146	0.204	4	5.72	42	184	<2	23	5.51	7	116	87	83	18.96	1.87	27	1.35	1328	9	77	113	361	>10.00	8	28	<10	1305	1578	48	67	<10	11	109
111554D	1304146	0.175	4	5.98	53	125	<2	57	5.69	11	129	90	89	25.81	2.13	29	1.47	1455	9	82	167	445	>10.00	6	16	<10	1463	2085	15	78	<10	13	125
111555	1304147	0.148	4	5.54	72	149	<2	46	4.20	11	93	83	115	29.25	1.64	28	1.19	1155	10	89	<100	259	>10.00	9	6	<10	621	994	48	44	<10	9	97
111556	1304148	0.135	3	5.06	40	108	<2	42	5.08	11	106	111	167	27.73	1.87	23	1.38	1340	16	125	<100	193	>10.00	11	14	<10	187	702	46	40	<10	9	114
111557	1304149	0.086	6	>10.00	17	344	<2	22	>10.00	5	35	151	75	11.74	2.37	154	3.28	2484	6	69	728	81	5.31	<5	17	<10	218	3094	20	297	<10	31	210

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, May 22, 2012

Certificate of Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 04/24/2012
 Date Completed: 05/03/2012
 Job #: 201241307
 Reference: TL 12 247
 Sample #: 132

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
111558	1304150	1.092	<1	>10.00	22	1020	<2	18	3.50	<4	14	119	546	3.68	2.00	35	1.11	604	53	35	623	72	0.76	<5	36	<10	224	1771	7	105	25	14	106
111559	1304151	0.154	3	>10.00	10	419	<2	23	8.96	6	60	114	241	16.22	2.03	118	2.79	1997	4	72	578	66	>10.00	<5	<5	<10	202	3507	<2	225	<10	29	142
111560	1304152	0.065	2	>10.00	11	271	<2	51	>10.00	<4	45	134	66	8.95	2.44	115	2.63	2084	3	67	725	38	1.53	<5	17	<10	183	6177	25	291	<10	35	132
111561	1304153	0.018	1	>10.00	7	252	<2	40	>10.00	<4	46	151	95	9.17	2.43	98	2.59	1853	5	73	725	17	1.25	<5	22	<10	197	4541	23	298	<10	35	127
111562	1304154	0.032	1	>10.00	9	213	<2	37	>10.00	<4	43	126	81	10.16	2.30	80	2.94	2202	2	66	717	27	2.57	5	17	<10	239	4069	20	245	12	35	122
111563	1304155	0.035	<1	>10.00	5	300	<2	27	>10.00	4	58	135	57	11.01	2.21	90	2.44	2414	<1	67	727	22	2.60	6	9	<10	220	3311	19	272	10	36	127
111564	1304156	0.023	<1	>10.00	7	206	<2	10	>10.00	4	40	132	64	11.29	2.48	81	2.48	2881	3	64	700	24	2.73	<5	15	<10	189	3315	12	282	<10	36	131
111565D	1304156	0.025	<1	>10.00	10	211	<2	48	>10.00	4	42	134	66	11.66	2.17	85	2.56	3034	2	64	700	22	2.77	<5	19	<10	198	3507	17	294	11	37	134
111566	1304157	0.095	1	>10.00	5	143	<2	31	>10.00	5	52	119	216	14.45	2.54	73	2.27	3889	3	72	655	27	5.83	5	17	<10	175	3718	3	266	<10	31	123
111567	1304158	0.263	2	>10.00	11	115	<2	20	8.34	6	123	123	174	14.98	2.02	75	1.89	1692	7	81	715	29	8.88	5	6	<10	132	3160	9	214	<10	28	95
111568	1304159	0.019	<1	>10.00	9	490	<2	46	>10.00	4	45	154	51	11.03	2.49	111	3.01	2263	4	74	739	20	1.75	5	13	<10	203	4657	17	341	<10	41	135
111569	1304160	<0.005	<1	>10.00	7	730	<2	33	5.06	<4	15	116	22	3.50	2.13	39	1.50	705	1	30	597	9	0.14	<5	35	<10	282	2790	21	117	20	17	62
111570	1304161	0.012	<1	>10.00	10	127	<2	31	>10.00	4	49	142	57	10.09	2.38	70	2.58	1811	4	77	747	21	0.67	<5	21	<10	224	4543	28	310	<10	36	137
111571	1304162	0.017	<1	>10.00	3	231	<2	33	>10.00	4	48	133	73	10.88	2.06	75	2.47	2246	2	70	729	19	1.23	<5	20	<10	202	3226	10	280	<10	35	162
111572	1304163	0.011	<1	>10.00	12	118	<2	25	>10.00	4	46	136	59	9.96	2.24	67	2.35	2402	2	64	783	16	0.66	<5	25	<10	211	4671	26	315	<10	34	132
111573	1304164	0.013	<1	>10.00	8	194	<2	44	>10.00	4	48	134	67	10.43	2.02	76	2.22	2289	1	66	742	19	1.27	5	18	<10	185	3317	14	285	<10	34	138
111574	1304165	0.017	<1	>10.00	5	85	<2	29	>10.00	4	49	127	80	10.69	2.52	75	2.23	2246	2	67	779	22	0.99	<5	21	<10	210	2851	4	304	<10	35	143
111575	1304166	0.009	<1	>10.00	6	223	<2	29	>10.00	4	53	122	88	10.31	2.25	85	2.48	2126	2	61	843	15	1.29	<5	25	<10	217	2966	34	303	<10	37	134
111576D	1304166	0.016	<1	>10.00	12	231	<2	46	>10.00	4	55	128	88	10.66	3.02	89	2.50	2233	2	60	846	21	1.28	<5	30	<10	244	3828	14	314	<10	37	137
111577	1304167	0.013	<1	>10.00	3	95	<2	33	>10.00	4	48	121	95	9.97	2.33	85	2.25	1755	3	61	882	17	1.08	<5	15	<10	263	3939	14	326	<10	35	148

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, May 22, 2012

Certificate of Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 04/24/2012
 Date Completed: 05/03/2012
 Job #: 201241307
 Reference: TL 12 247
 Sample #: 132

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
111578	1304168	<0.005	<1	>10.00	11	792	<2	18	4.59	<4	9	59	16	2.35	2.20	91	1.09	565	4	37	431	13	0.39	<5	35	<10	219	1766	8	53	<10	8	56
111579	1304169	<0.005	<1	>10.00	12	699	<2	31	3.86	<4	5	62	6	1.66	1.90	79	0.74	385	7	40	384	21	0.50	<5	37	<10	191	1184	3	32	<10	5	85
111580	1304170	0.219	<1	4.74	426	>5000	<2	10	2.14	<4	6	49	29	2.89	1.94	23	0.23	<100	24	11	<100	21	0.49	18	29	<10	108	615	22	15	39	7	27
111581	1304171	0.006	<1	>10.00	9	900	<2	20	4.52	<4	8	67	20	2.33	2.06	72	0.75	477	9	41	431	31	0.68	<5	32	<10	206	1538	5	50	<10	7	129
111582	1304172	0.008	<1	>10.00	12	689	<2	29	5.67	<4	15	67	23	3.46	1.82	75	1.05	644	3	35	461	21	0.41	<5	39	<10	226	2186	10	96	<10	12	77
111583	1304173	0.009	<1	>10.00	9	316	<2	30	>10.00	4	56	117	110	10.58	2.27	86	2.10	1843	2	69	920	24	0.84	5	16	<10	256	4016	7	337	<10	40	154
111584	1304174	0.016	1	>10.00	8	199	<2	55	>10.00	6	58	109	114	11.44	2.15	78	2.52	2421	3	60	857	221	1.64	7	21	<10	229	3285	12	307	<10	38	370
111585	1304175	0.029	<1	>10.00	9	73	<2	42	>10.00	4	56	114	122	11.36	2.24	76	2.15	2277	3	62	860	30	1.63	5	16	<10	216	3322	11	315	<10	38	146
111586	1304176	0.009	<1	>10.00	8	61	<2	31	>10.00	4	49	112	128	10.74	2.03	70	2.09	2230	<1	58	862	25	1.62	<5	17	<10	193	2528	9	294	<10	37	130
111587D	1304176	0.013	<1	>10.00	9	69	<2	34	>10.00	4	49	112	132	10.90	2.30	73	2.14	2276	<1	56	868	21	1.67	<5	26	<10	203	2641	15	301	<10	38	133
111588	1304177	0.025	<1	>10.00	8	239	<2	32	>10.00	4	48	103	89	10.46	2.34	75	2.21	2061	<1	50	911	20	1.29	6	7	<10	195	3035	9	310	<10	39	134
111589	1304178	0.038	<1	>10.00	9	109	<2	39	>10.00	5	56	93	353	13.05	2.27	64	1.81	2173	<1	61	733	29	3.57	<5	7	<10	202	2780	6	285	<10	32	137
111590	1304179	0.010	<1	>10.00	13	101	<2	36	>10.00	<4	44	99	77	10.13	1.96	74	2.09	2086	<1	47	909	19	0.81	<5	17	<10	185	3111	12	298	<10	39	132
111591	1304180	<0.005	<1	>10.00	10	682	<2	31	4.87	<4	15	111	24	3.37	2.28	37	1.41	664	<1	28	582	12	0.13	<5	38	<10	251	2508	21	109	17	16	57
111592	1304181	0.179	2	9.81	6	58	<2	41	6.00	6	73	76	480	16.58	2.03	69	1.82	2640	1	81	408	36	8.49	7	<5	<10	106	1595	9	110	<10	16	140
111593	1304182	0.525	2	>10.00	8	66	<2	23	5.23	5	38	83	177	13.27	2.59	78	2.09	4903	5	60	365	31	4.39	5	8	<10	70	1327	11	130	<10	18	232
111594	1304183	0.540	<1	>10.00	9	236	<2	40	9.81	4	52	96	100	10.40	2.82	122	2.64	1885	<1	52	1284	24	1.47	5	15	<10	173	3359	20	326	<10	46	165
111595	1304184	0.020	<1	>10.00	6	219	<2	29	>10.00	4	49	81	84	9.99	2.18	95	2.35	2024	<1	47	907	20	0.92	<5	20	<10	222	3703	6	308	<10	39	145
111596	1304185	0.013	<1	>10.00	5	591	<2	25	6.96	<4	31	65	46	6.04	2.24	113	1.97	1297	<1	31	792	8	0.70	<5	23	<10	136	4443	23	202	<10	33	94
111597	1304186	0.025	<1	>10.00	6	385	<2	32	>10.00	<4	36	89	77	7.62	2.59	121	2.07	1507	<1	35	1021	13	0.60	<5	27	<10	190	4139	9	262	<10	42	103

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Tuesday, May 22, 2012

Certificate of Analysis

Treasury Metals Inc
Exchange Tower 130 King St Suite 3680
Toronto, On, CAN
M5X 1B1
Ph#: (416) 599-4133
Fax#: (416) 599-4959
Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 04/24/2012
Date Completed: 05/03/2012
Job #: 201241307
Reference: TL 12 247
Sample #: 132

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
111598D	1304186	0.023	<1	>10.00	4	370	<2	33	>10.00	<4	34	87	76	7.24	2.50	116	2.02	1412	<1	34	1012	14	0.55	<5	32	<10	172	3497	15	247	<10	41	98
111599	1304187	0.009	<1	>10.00	10	431	<2	21	9.87	<4	30	83	75	6.38	2.40	97	1.70	1584	<1	32	907	13	0.43	<5	24	<10	200	3327	19	212	<10	37	93
111600	1304188	0.116	<1	>10.00	3	391	<2	36	>10.00	<4	43	130	105	9.15	2.32	76	2.56	1521	<1	49	927	12	0.58	<5	18	<10	155	2910	10	299	<10	36	127
111601	1304189	0.197	<1	>10.00	3	48	<2	27	>10.00	<4	43	133	117	9.36	2.34	80	2.68	1223	<1	47	935	18	0.57	5	21	<10	171	2801	18	306	<10	37	110
111602	1304190	3.354	1	>10.00	387	2012	<2	27	4.95	<4	12	230	77	3.30	2.49	38	1.17	465	28	51	752	23	1.03	37	39	<10	177	1637	16	119	10	13	220
111603	1304191	0.013	<1	>10.00	16	175	<2	29	8.20	4	44	136	108	9.37	2.41	91	2.99	1204	<1	50	935	16	0.54	<5	9	<10	279	3172	18	302	<10	37	114
111604	1304192	0.010	<1	>10.00	13	2150	<2	19	>10.00	<4	37	102	91	8.06	2.41	64	2.51	1481	<1	35	831	15	1.02	<5	19	<10	1244	4112	18	246	<10	34	117
111605	1304193	<0.005	<1	>10.00	6	273	<2	16	9.14	<4	47	53	85	8.29	2.24	48	2.36	1105	<1	30	1109	19	0.72	<5	13	<10	399	5921	15	271	16	41	149
111606	1304194	0.014	<1	>10.00	9	215	<2	25	>10.00	<4	39	92	89	7.98	2.24	57	2.53	1210	<1	38	951	23	0.41	<5	16	<10	466	4289	8	254	<10	36	132
111607	1304195	0.006	<1	>10.00	13	118	<2	38	>10.00	<4	42	148	97	8.14	2.07	72	2.53	1316	<1	55	849	15	0.40	<5	17	<10	351	2866	14	227	<10	34	103
111608	1304196	0.008	<1	2.83	<2	<1	4	16	4.32	<4	44	77	108	8.79	<0.01	27	2.52	1273	<1	58	966	19	0.41	<5	<5	<10	267	3169	<2	242	<10	33	122
111609R	1304196	0.006	<1	3.33	<2	<1	4	17	4.63	<4	44	82	104	9.41	<0.01	29	2.69	1388	<1	62	988	17	0.43	<5	<5	<10	297	3747	<2	259	<10	35	121
111610	1304197	0.020	<1	3.88	3	<1	3	33	5.28	<4	43	68	92	8.92	0.02	34	2.60	1343	<1	60	906	14	0.40	<5	<5	<10	329	3672	5	258	<10	32	114
111611	1304198	0.007	<1	4.08	5	16	4	26	4.73	<4	48	64	113	9.37	0.05	35	2.75	1247	<1	63	911	17	0.72	5	<5	<10	222	4033	4	284	<10	31	121
111612	1304199	0.007	<1	4.28	6	74	4	17	4.53	<4	45	58	124	8.89	0.09	32	2.11	1320	<1	55	920	17	0.91	<5	<5	<10	194	3612	3	276	<10	32	122
111613	1304200	<0.005	<1	3.88	6	320	2	18	2.23	<4	15	55	23	3.51	0.20	9	1.43	689	<1	32	616	9	0.10	<5	9	<10	235	2705	9	112	15	15	63
111614	1304201	0.011	<1	4.27	3	57	3	20	5.13	<4	47	56	90	9.41	0.39	32	1.80	1830	<1	53	937	16	0.90	<5	<5	<10	180	4061	<2	282	<10	33	141
111615	1304202	0.027	<1	3.44	<2	33	3	30	4.85	<4	40	54	87	8.14	<0.01	26	2.06	1275	<1	44	952	11	0.41	<5	<5	<10	176	2924	<2	272	<10	32	110
111616	1304203	0.008	<1	3.84	<2	94	4	29	6.04	<4	46	54	103	9.83	0.37	35	2.58	2333	<1	48	858	17	1.34	<5	<5	<10	202	4482	4	281	<10	30	132
111617	1304204	0.237	<1	1.63	2	3	3	19	4.67	<4	38	53	78	8.50	<0.01	20	2.33	1215	<1	44	947	13	0.33	<5	<5	<10	169	1773	4	274	<10	32	110

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
Jason Moore, General Manager

The results included on this report relate only to the items tested
The Certificate of Analysis should not be reproduced except in full,
without the written approval of the laboratory

Tuesday, May 22, 2012


Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/24/2012
 Date Completed: 05/03/2012
 Job #: 201241307
 Reference: TL 12 247
 Sample #: 132

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
111618	1304205	0.009	<1	3.19	4	29	3	28	4.58	<4	39	61	91	7.87	<0.01	26	2.11	1185	<1	61	869	13	0.38	<5	<5	<10	153	2044	<2	243	<10	29	104
111619	1304206	0.016	<1	4.64	3	65	3	22	4.63	<4	48	56	108	8.93	0.40	40	2.22	1539	<1	63	899	14	0.76	<5	<5	<10	176	3628	<2	274	<10	32	139
111620D	1304206	0.019	<1	4.27	<2	65	3	23	4.72	<4	50	57	111	9.32	0.61	40	2.27	1648	<1	68	943	17	0.74	<5	<5	<10	170	4428	<2	284	<10	32	144
111621	1304207	0.038	<1	4.71	<2	77	4	27	5.04	4	55	54	85	10.34	0.42	57	3.09	2088	<1	54	1016	16	1.13	<5	<5	<10	196	7341	<2	347	11	37	158
111622	1304208	0.023	<1	3.53	<2	75	3	35	5.02	<4	53	65	87	10.27	<0.01	56	3.51	1899	<1	58	937	17	1.10	<5	<5	<10	155	6018	10	319	<10	29	160

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Thursday, May 3, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/24/2012
 Date Completed: 05/03/2012
 Job #: 201241307
 Reference: TL 12 247
 Sample #: 132

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
111478	1304077	35	0.001	0.035
111479	1304078	152	0.004	0.152
111480	1304079	522	0.015	0.522
111481	1304080	<5	<0.001	<0.005
111482	1304081	162	0.005	0.162
111483	1304082	201	0.006	0.201
111484	1304083	7916	0.231	7.916
111485	1304084	90	0.003	0.090
111486	1304085	16	<0.001	0.016
111487	1304086	34	0.001	0.034
111488 Dup	1304086	31	<0.001	0.031
111489	1304087	15	<0.001	0.015
111490	1304088	22	<0.001	0.022
111491	1304089	14	<0.001	0.014
111492	1304090	Insufficient Sample		
111493	1304091	12	<0.001	0.012
111494	1304092	30	<0.001	0.030
111495	1304093	8	<0.001	0.008
111496	1304094	<5	<0.001	<0.005
111497	1304095	150	0.004	0.150
111498	1304096	56	0.002	0.056
111499 Dup	1304096	52	0.002	0.052
111500	1304097	70	0.002	0.070
111501	1304098	13	<0.001	0.013
111502	1304099	104	0.003	0.104
111503	1304100	<5	<0.001	<0.005
111504	1304101	120	0.004	0.120
111505	1304102	191	0.006	0.191
111506	1304103	42	0.001	0.042
111507	1304104	38	0.001	0.038

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Thursday, May 3, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/24/2012
 Date Completed: 05/03/2012
 Job #: 201241307
 Reference: TL 12 247
 Sample #: 132

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
111508	1304105	107	0.003	0.107
111509	1304106	49	0.001	0.049
111510 Dup	1304106	34	<0.001	0.034
111511	1304107	20	<0.001	0.020
111512	1304108	38	0.001	0.038
111513	1304109	6	<0.001	0.006
111514	1304110	224	0.007	0.224
111515	1304111	10	<0.001	0.010
111516	1304112	38	0.001	0.038
111517	1304113	24	<0.001	0.024
111518	1304114	39	0.001	0.039
111519	1304115	13	<0.001	0.013
111520	1304116	18	<0.001	0.018
111521 Dup	1304116	18	<0.001	0.018
111522	1304117	114	0.003	0.114
111523	1304118	27	<0.001	0.027
111524	1304119	25	<0.001	0.025
111525	1304120	6	<0.001	0.006
111526	1304121	30	<0.001	0.030
111527	1304122	19	<0.001	0.019
111528	1304123	12	<0.001	0.012
111529	1304124	17	<0.001	0.017
111530	1304125	248	0.007	0.248
111531	1304126	91	0.003	0.091
111532 Dup	1304126	102	0.003	0.102
111533	1304127	27	<0.001	0.027
111534	1304128	50	0.001	0.050
111535	1304129	59	0.002	0.059
111536	1304130	3522	0.103	3.522
111537	1304131	28	<0.001	0.028

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Thursday, May 3, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/24/2012
 Date Completed: 05/03/2012
 Job #: 201241307
 Reference: TL 12 247
 Sample #: 132

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
111538	1304132	59	0.002	0.059
111539	1304133	26	<0.001	0.026
111540	1304134	18	<0.001	0.018
111541	1304135	29	<0.001	0.029
111542	1304136	36	0.001	0.036
111543 Rep	1304136	31	<0.001	0.031
111544	1304137	18	<0.001	0.018
111545	1304138	31	<0.001	0.031
111546	1304139	48	0.001	0.048
111547	1304140	6	<0.001	0.006
111548	1304141	25	<0.001	0.025
111549	1304142	23	<0.001	0.023
111550	1304143	36	0.001	0.036
111551	1304144	25	<0.001	0.025
111552	1304145	43	0.001	0.043
111553	1304146	204	0.006	0.204
111554 Dup	1304146	175	0.005	0.175
111555	1304147	148	0.004	0.148
111556	1304148	135	0.004	0.135
111557	1304149	86	0.002	0.086
111558	1304150	1092	0.032	1.092
111559	1304151	154	0.004	0.154
111560	1304152	65	0.002	0.065
111561	1304153	18	<0.001	0.018
111562	1304154	32	<0.001	0.032
111563	1304155	35	0.001	0.035
111564	1304156	23	<0.001	0.023
111565 Dup	1304156	25	<0.001	0.025
111566	1304157	95	0.003	0.095
111567	1304158	263	0.008	0.263

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Thursday, May 3, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/24/2012
 Date Completed: 05/03/2012
 Job #: 201241307
 Reference: TL 12 247
 Sample #: 132

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
111568	1304159	19	<0.001	0.019
111569	1304160	<5	<0.001	<0.005
111570	1304161	12	<0.001	0.012
111571	1304162	17	<0.001	0.017
111572	1304163	11	<0.001	0.011
111573	1304164	13	<0.001	0.013
111574	1304165	17	<0.001	0.017
111575	1304166	9	<0.001	0.009
111576 Dup	1304166	16	<0.001	0.016
111577	1304167	13	<0.001	0.013
111578	1304168	<5	<0.001	<0.005
111579	1304169	<5	<0.001	<0.005
111580	1304170	219	0.006	0.219
111581	1304171	6	<0.001	0.006
111582	1304172	8	<0.001	0.008
111583	1304173	9	<0.001	0.009
111584	1304174	16	<0.001	0.016
111585	1304175	29	<0.001	0.029
111586	1304176	9	<0.001	0.009
111587 Dup	1304176	13	<0.001	0.013
111588	1304177	25	<0.001	0.025
111589	1304178	38	0.001	0.038
111590	1304179	10	<0.001	0.010
111591	1304180	<5	<0.001	<0.005
111592	1304181	179	0.005	0.179
111593	1304182	525	0.015	0.525
111594	1304183	540	0.016	0.540
111595	1304184	20	<0.001	0.020
111596	1304185	13	<0.001	0.013
111597	1304186	25	<0.001	0.025

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Thursday, May 3, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 04/24/2012
 Date Completed: 05/03/2012
 Job #: 201241307
 Reference: TL 12 247
 Sample #: 132

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
111598 Dup	1304186	23	<0.001	0.023
111599	1304187	9	<0.001	0.009
111600	1304188	116	0.003	0.116
111601	1304189	197	0.006	0.197
111602	1304190	3354	0.098	3.354
111603	1304191	13	<0.001	0.013
111604	1304192	10	<0.001	0.010
111605	1304193	<5	<0.001	<0.005
111606	1304194	14	<0.001	0.014
111607	1304195	6	<0.001	0.006
111608	1304196	8	<0.001	0.008
111609 Rep	1304196	6	<0.001	0.006
111610	1304197	20	<0.001	0.020
111611	1304198	7	<0.001	0.007
111612	1304199	7	<0.001	0.007
111613	1304200	<5	<0.001	<0.005
111614	1304201	11	<0.001	0.011
111615	1304202	27	<0.001	0.027
111616	1304203	8	<0.001	0.008
111617	1304204	237	0.007	0.237
111618	1304205	9	<0.001	0.009
111619	1304206	16	<0.001	0.016
111620 Dup	1304206	19	<0.001	0.019
111621	1304207	38	0.001	0.038
111622	1304208	23	<0.001	0.023

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested
 The Certificate of Analysis should not be reproduced except in full,
 without the written approval of the laboratory

Wednesday, July 18, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/15/2012
 Date Completed: 06/27/2012
 Job #: 201242109
 Reference: TK 12 248
 Sample #: 252

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
170423	1360302	0.008	<1	4.35	5	<1	3	19	5.15	6	44	47	75	12.46	<0.01	27	2.60	3023	<1	55	759	16	0.77	5	<5	<10	183	5246	2	283	<10	43	121
170424	1360303	0.016	<1	1.61	6	14	3	9	4.46	5	44	50	100	10.57	<0.01	15	2.32	2255	<1	68	877	9	0.54	7	<5	<10	118	4400	<2	287	<10	45	117
170425	1360304	<0.005	<1	2.64	10	52	2	23	3.85	4	48	45	95	8.46	<0.01	22	2.34	1607	<1	52	859	10	0.40	8	<5	<10	162	5737	5	311	<10	41	190
170426	1360305	<0.005	<1	2.18	2	73	2	19	4.55	4	46	50	86	8.15	<0.01	19	2.40	1912	<1	63	805	11	0.40	6	<5	<10	162	6256	<2	301	<10	39	133
170427	1360306	0.019	<1	2.87	7	27	2	6	4.92	4	45	54	105	8.42	<0.01	24	2.51	1898	<1	63	786	13	0.82	6	<5	<10	159	5183	<2	289	<10	37	131
170428	1360307	0.017	<1	2.11	3	<1	2	6	4.58	4	42	50	91	8.31	<0.01	18	2.47	1685	<1	57	861	9	0.41	<5	<5	<10	149	4910	<2	271	<10	40	111
170429	1360308	0.032	<1	2.80	<2	19	2	3	5.07	4	46	60	110	8.84	<0.01	16	2.54	2115	<1	73	843	11	0.48	5	<5	<10	149	6120	10	287	<10	38	126
170430	1360309	0.008	<1	3.35	<2	215	3	6	5.46	6	48	79	93	11.86	<0.01	29	2.53	2887	<1	62	776	15	0.72	5	<5	<10	179	7473	<2	292	<10	38	293
170431	1360310	0.008	<1	1.35	5	261	2	13	1.97	<4	16	51	22	3.42	<0.01	5	1.36	695	<1	27	587	7	0.30	<5	<5	<10	194	2631	<2	109	11	15	57
170432	1360311	0.009	<1	3.32	2	87	2	12	5.03	4	42	77	78	8.07	<0.01	15	2.16	1840	<1	59	846	9	0.70	5	12	<10	127	4817	4	270	<10	36	203
170433D	1360311	0.017	<1	6.59	<2	105	2	<1	5.52	4	42	78	75	8.24	<0.01	22	2.27	1919	<1	57	841	12	0.93	6	<5	<10	173	5898	<2	287	<10	39	204
170434	1360312	0.068	<1	1.93	12	<1	2	19	4.56	4	38	54	82	8.77	<0.01	13	2.39	1317	<1	53	936	12	0.43	6	<5	<10	123	2723	5	289	<10	43	118
170435	1360313	0.023	<1	4.13	4	383	2	4	4.25	4	48	68	139	8.67	<0.01	32	1.71	1611	<1	71	974	15	0.91	5	<5	<10	181	6266	<2	311	<10	43	282
170436	1360314	0.069	<1	4.26	6	165	2	22	6.06	4	48	88	87	9.08	<0.01	20	2.36	1568	<1	73	785	7	0.45	9	<5	<10	194	6598	<2	294	<10	37	138
170437	1360315	0.029	<1	2.73	4	<1	2	12	4.85	4	46	84	97	8.99	<0.01	21	2.91	1341	<1	74	794	7	0.42	<5	<5	<10	116	4982	<2	283	<10	35	129
170438	1360316	0.014	<1	2.15	8	<1	2	11	4.52	4	45	78	97	8.66	<0.01	19	2.86	1314	<1	58	785	5	0.39	7	<5	<10	101	4929	<2	280	<10	34	123
170439	1360317	0.011	<1	2.98	13	<1	3	22	4.92	5	52	53	130	10.35	<0.01	22	2.74	1535	<1	73	950	14	0.62	5	9	<10	112	6685	<2	334	<10	40	142
170440	1360318	0.011	<1	3.06	7	<1	2	17	4.90	5	50	60	101	9.19	<0.01	16	2.71	1421	<1	56	819	8	0.61	6	<5	<10	145	6598	<2	303	<10	36	134
170441	1360319	0.009	<1	3.23	8	76	2	4	5.31	<4	45	104	75	7.08	<0.01	21	2.39	1205	<1	57	759	8	1.04	<5	<5	<10	210	7267	<2	273	<10	32	130
170442	1360320	0.242	<1	<0.01	429	>5000	2	2	0.75	<4	6	18	30	2.92	<0.01	<1	0.22	<100	<1	9	<100	21	0.63	13	<5	<10	132	741	9	17	44	7	17

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By:  Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, July 18, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/15/2012
 Date Completed: 06/27/2012
 Job #: 201242109
 Reference: TK 12 248
 Sample #: 252

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
170443	1360321	<0.005	<1	1.11	<2	229	2	<1	2.30	<4	22	77	31	4.40	<0.01	16	1.42	685	<1	63	314	5	0.61	<5	<5	<10	83	3442	<2	156	<10	13	74
170444D	1360321	<0.005	<1	0.15	4	115	<2	1	2.23	<4	23	77	32	4.42	<0.01	13	1.39	684	<1	64	306	5	0.51	7	<5	<10	74	3392	<2	157	<10	12	83
170445	1360322	0.030	<1	3.15	3	467	3	3	8.04	4	65	98	228	8.48	<0.01	41	2.32	1806	<1	64	786	10	2.10	5	<5	<10	173	6518	5	287	<10	31	164
170446	1360323	0.009	<1	3.86	9	357	3	2	4.59	<4	55	118	69	5.02	<0.01	27	1.74	1308	<1	74	755	6	0.61	7	<5	<10	125	5695	2	319	<10	29	119
170447	1360324	0.025	<1	7.43	17	368	2	<1	4.56	<4	59	118	118	7.32	<0.01	37	2.14	2064	<1	85	877	8	0.93	8	5	<10	116	7607	5	361	<10	35	166
170448	1360325	0.011	<1	3.77	13	189	2	18	5.30	4	46	83	113	8.76	<0.01	18	2.32	2247	<1	67	816	10	0.67	5	<5	<10	112	5510	<2	286	<10	36	187
170449	1360326	0.010	<1	4.65	<2	42	3	8	5.83	5	48	81	109	9.24	<0.01	24	2.87	1764	<1	71	808	7	0.59	<5	<5	<10	144	5998	<2	288	<10	37	165
170450	1360327	0.026	<1	3.48	<2	<1	2	9	5.63	5	50	84	110	9.84	<0.01	17	2.94	2298	<1	72	796	15	0.54	6	<5	<10	177	6195	<2	307	<10	34	278
170451	1360328	0.028	<1	4.59	2	<1	2	8	5.22	5	51	85	90	9.99	<0.01	29	3.02	1767	<1	74	804	14	0.48	7	<5	<10	210	7181	<2	305	<10	34	120
170452	1360329	0.019	<1	3.79	12	<1	2	13	5.07	5	50	83	93	10.56	<0.01	26	3.27	1629	<1	63	808	11	0.46	<5	<5	<10	195	6581	<2	353	<10	36	134
170453	1360330	<0.005	<1	3.79	7	359	2	18	2.31	<4	17	53	22	3.47	<0.01	9	1.45	702	<1	27	586	7	0.39	<5	8	<10	268	2927	<2	115	19	16	48
170454	1360331	0.066	<1	3.86	4	<1	3	14	6.11	5	51	86	98	9.41	<0.01	28	2.84	1635	<1	72	829	9	0.49	<5	<5	<10	178	6952	3	355	<10	37	108
170455D	1360331	0.019	<1	4.09	8	<1	3	2	6.00	5	49	83	97	9.15	<0.01	29	2.80	1582	<1	72	816	5	0.55	5	<5	<10	172	6385	<2	343	<10	37	101
170456	1360332	0.014	<1	3.29	5	<1	2	28	5.53	5	48	81	101	9.04	<0.01	18	2.55	1929	<1	68	801	13	0.45	6	<5	<10	186	5537	5	312	<10	34	154
170457	1360333	0.020	<1	3.71	8	<1	2	19	5.77	5	49	83	89	9.54	<0.01	18	2.85	1776	<1	70	851	10	0.44	5	5	<10	187	5855	2	320	<10	35	134
170458	1360334	0.035	<1	2.53	10	<1	3	7	5.51	5	46	75	88	9.57	<0.01	22	3.02	1377	<1	57	833	13	0.33	6	<5	<10	184	3216	2	307	<10	34	114
170459	1360335	0.162	<1	4.60	7	3	2	12	5.67	5	50	88	104	9.60	<0.01	23	2.73	1561	<1	65	913	12	0.62	5	<5	<10	197	6128	<2	327	<10	37	125
170460	1360336	0.105	<1	3.42	14	<1	3	8	5.91	5	48	86	85	9.42	<0.01	18	2.69	1504	<1	66	919	9	0.46	6	<5	<10	158	5362	<2	307	<10	36	120
170461	1360337	0.014	<1	3.92	12	195	2	21	5.35	5	51	64	114	8.83	<0.01	23	2.33	2184	<1	79	904	10	0.86	7	<5	<10	128	5656	4	268	<10	35	229
170462	1360338	0.013	<1	4.85	2	58	2	<1	5.91	5	52	80	129	9.45	<0.01	16	2.40	2213	<1	86	857	8	0.76	5	<5	<10	141	6375	3	291	<10	36	200

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, July 18, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/15/2012
 Date Completed: 06/27/2012
 Job #: 201242109
 Reference: TK 12 248
 Sample #: 252

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
170463	1360339	0.040	<1	4.23	<2	86	3	<1	5.03	5	36	36	68	11.33	<0.01	20	2.03	3067	<1	49	985	10	0.85	7	7	<10	103	5506	2	200	<10	57	173
170464	1360340	1.761	<1	2.92	15	318	2	<1	2.07	<4	17	51	31	3.87	<0.01	9	1.43	755	<1	29	602	11	0.41	7	6	<10	221	2711	3	113	17	16	61
170465	1360341	0.007	<1	2.73	3	113	2	24	3.69	<4	29	35	44	6.81	<0.01	13	1.66	1586	<1	41	1061	6	0.39	6	<5	<10	104	4476	3	212	<10	50	117
170466D	1360341	0.013	<1	3.87	5	120	2	18	4.05	4	31	37	46	7.17	<0.01	16	1.76	1672	<1	43	1116	9	0.48	7	<5	<10	116	4719	<2	225	<10	54	118
170467	1360342	0.015	<1	3.92	2	127	2	9	4.07	<4	37	53	59	7.15	<0.01	16	2.15	1906	<1	57	1049	11	0.47	6	6	<10	123	4821	<2	271	<10	44	160
170468	1360343	0.011	<1	3.78	12	168	3	9	5.63	4	41	58	133	7.78	<0.01	17	1.96	2238	<1	66	899	9	0.51	6	7	<10	180	6500	4	262	<10	36	166
170469	1360344	0.012	<1	4.13	<2	199	3	19	5.78	5	50	80	96	8.80	<0.01	25	2.43	1921	<1	78	981	13	0.68	6	<5	<10	153	6146	<2	333	<10	39	146
170470	1360345	0.019	<1	2.84	13	281	3	16	4.10	4	54	71	91	8.92	<0.01	36	2.78	1760	<1	63	945	14	0.91	5	<5	<10	112	4581	<2	330	<10	35	214
170471	1360346	0.034	<1	3.06	5	275	3	10	4.95	4	48	66	88	7.99	<0.01	34	2.72	2017	<1	73	937	8	1.06	5	<5	<10	130	5407	4	298	11	35	227
170472	1360347	0.149	1	4.19	9	231	3	2	5.47	4	52	73	122	9.86	<0.01	25	2.67	2297	<1	69	963	13	1.27	6	7	<10	155	5854	2	330	<10	38	204
170473	1360348	0.014	<1	3.37	<2	162	3	14	5.36	5	48	76	129	9.41	<0.01	20	2.63	1682	<1	73	977	11	0.73	<5	<5	<10	154	5515	3	317	<10	39	141
170474	1360349	0.012	<1	2.69	6	12	3	19	5.73	5	45	66	108	9.59	<0.01	12	2.66	1429	<1	60	940	8	0.57	7	5	<10	147	4587	<2	302	<10	38	119
170475	1360350	<0.005	<1	3.72	10	323	2	6	2.26	<4	16	51	22	3.40	<0.01	10	1.43	687	<1	28	593	10	0.46	<5	5	<10	244	2745	<2	112	19	16	53
170476	1360351	0.024	<1	2.86	4	56	3	30	5.41	5	49	72	132	10.36	<0.01	16	2.75	2148	<1	65	969	10	0.92	7	<5	<10	138	4438	2	315	<10	39	240
170477D	1360351	0.028	<1	3.64	5	58	2	9	5.49	5	49	72	131	10.31	<0.01	19	2.76	2158	<1	67	962	12	1.00	<5	<5	<10	151	4674	6	321	<10	39	239
170478	1360352	0.022	<1	6.36	15	120	3	21	5.80	6	57	77	103	10.20	<0.01	27	2.57	2181	<1	64	973	14	0.89	7	5	<10	173	9520	<2	351	<10	42	246
170479	1360353	0.005	<1	5.78	14	152	2	17	5.68	5	61	78	116	9.24	<0.01	30	2.15	2652	<1	83	937	14	0.82	<5	<5	<10	202	9290	2	340	<10	36	224
170480	1360354	<0.005	<1	5.59	13	104	3	7	5.98	4	58	76	101	9.60	<0.01	25	2.49	2486	<1	80	919	11	0.71	5	<5	<10	183	8699	<2	354	<10	36	172
170481	1360355	0.022	<1	5.69	<2	167	3	2	5.27	4	56	78	147	9.47	<0.01	51	2.83	2283	<1	82	917	15	0.97	<5	<5	<10	156	7880	<2	352	<10	35	179
170482	1360356	0.018	<1	5.22	6	187	2	11	5.19	5	57	74	166	9.70	<0.01	51	2.93	2364	<1	73	913	10	0.98	<5	<5	<10	158	7576	3	357	<10	35	179

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, July 18, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/15/2012
 Date Completed: 06/27/2012
 Job #: 201242109
 Reference: TK 12 248
 Sample #: 252

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
170483	1360357	<0.005	<1	4.20	5	102	3	13	5.29	4	46	73	87	7.98	<0.01	21	2.20	2080	<1	67	823	11	0.51	8	<5	<10	160	7160	<2	300	<10	31	127
170484	1360358	0.010	<1	4.55	8	80	2	9	4.56	4	48	69	93	8.28	<0.01	39	2.17	1938	<1	66	960	6	1.14	9	<5	<10	260	8588	4	306	<10	37	187
170485	1360359	0.014	<1	5.09	8	119	3	15	4.98	9	52	78	159	8.30	<0.01	42	1.75	2397	<1	77	1015	14	1.23	<5	<5	<10	201	8355	2	328	11	38	943
170486	1360360	4.730	68	2.79	46	408	2	5	1.35	20	15	35	53	3.46	<0.01	7	0.92	556	<1	25	550	585	0.71	45	<5	233	229	2113	<2	96	55	14	1790
170487	1360361	0.025	1	4.58	<2	42	2	16	4.51	5	47	73	111	8.57	<0.01	26	2.19	2208	<1	84	908	21	0.78	<5	<5	<10	149	5904	2	275	<10	35	433
170488R	1360361	0.011	<1	5.00	4	36	3	17	4.90	6	49	76	115	9.07	<0.01	29	2.37	2267	<1	89	963	18	0.78	6	5	<10	158	4658	<2	304	<10	38	437
170489	1360362	0.035	<1	2.91	<2	19	2	<1	4.99	17	46	67	130	10.04	<0.01	20	2.18	2404	<1	92	784	15	1.50	5	<5	<10	120	3895	3	289	26	39	2576
170490	1360363	0.008	<1	5.64	3	88	3	8	5.69	6	59	80	80	9.49	<0.01	23	1.90	2621	<1	83	964	20	0.67	7	6	<10	168	8926	<2	345	<10	36	337
170491	1360364	0.026	<1	5.37	2	152	2	8	5.37	5	54	73	100	9.39	<0.01	22	1.74	2207	<1	82	1009	9	0.79	5	<5	<10	161	9255	4	329	<10	35	308
170492	1360365	0.028	<1	5.56	2	14	3	23	6.29	5	55	74	114	10.39	<0.01	25	2.62	1866	<1	75	938	13	0.70	7	<5	<10	216	8658	<2	349	<10	41	168
170493	1360366	0.007	<1	6.06	14	<1	3	1	4.97	6	54	77	99	11.56	<0.01	37	3.27	1727	<1	72	979	12	0.66	7	5	<10	302	8366	9	363	<10	42	167
170494	1360367	<0.005	<1	6.27	5	<1	3	3	4.36	5	56	75	97	11.34	0.07	39	3.29	1732	<1	69	985	5	0.67	7	<5	<10	345	9122	2	373	<10	41	121
170495	1360368	<0.005	<1	8.31	4	<1	2	28	4.46	5	53	76	88	11.01	<0.01	46	3.48	1600	<1	71	986	10	0.84	7	<5	<10	329	9000	7	362	<10	43	109
170496	1360369	<0.005	<1	6.35	10	<1	3	12	4.90	6	54	65	92	11.26	<0.01	48	2.82	1746	<1	68	949	10	0.94	5	<5	<10	331	9991	4	372	<10	34	152
170497	1360370	<0.005	<1	6.67	6	383	2	27	2.60	<4	17	54	21	3.40	<0.01	22	1.45	703	<1	28	582	10	0.72	<5	<5	<10	304	3276	2	116	22	15	51
170498	1360371	0.008	1	6.54	<2	<1	3	18	4.43	5	51	28	81	11.25	<0.01	41	2.63	1617	<1	46	1056	6	0.90	7	<5	<10	250	9431	6	359	<10	38	129
170499D	1360371	0.005	1	6.55	5	6	4	20	4.65	6	53	31	85	11.56	<0.01	48	2.45	1642	<1	52	1100	13	1.13	<5	<5	<10	261	8809	4	375	<10	32	130
170500	1360372	0.007	1	7.34	11	5	3	20	5.24	5	50	66	105	10.30	<0.01	36	2.59	1559	<1	67	922	13	1.20	11	<5	<10	242	7385	<2	350	<10	34	132
170501	1360373	<0.005	2	5.87	4	1	3	22	5.08	5	51	92	113	9.45	<0.01	33	2.47	1534	<1	80	758	12	1.02	6	<5	<10	243	7062	3	291	<10	27	118
170502	1360374	0.010	<1	6.66	<2	<1	3	15	5.89	5	55	98	98	10.22	0.08	26	3.12	1648	<1	95	805	13	0.80	7	<5	<10	227	8110	<2	304	<10	35	125

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, July 18, 2012

Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/15/2012
 Date Completed: 06/27/2012
 Job #: 201242109
 Reference: TK 12 248
 Sample #: 252

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
170503	1360375	0.020	<1	4.93	8	165	3	3	6.56	5	51	77	155	9.20	<0.01	24	2.98	1771	<1	94	800	11	1.32	<5	<5	<10	191	6581	<2	273	10	34	355
170504	1360376	0.032	<1	6.74	7	221	3	<1	7.07	6	53	88	182	9.33	<0.01	37	2.98	1915	<1	94	802	18	1.75	6	5	<10	223	7920	<2	298	11	32	365
170505	1360377	0.005	1	6.27	10	100	3	12	6.00	6	60	82	103	10.73	0.04	42	3.06	1980	<1	105	823	15	1.26	<5	<5	<10	203	8963	<2	315	<10	31	225
170506	1360378	0.013	1	7.62	4	37	3	10	6.25	5	61	77	123	11.23	0.15	35	3.16	1922	<1	94	875	14	1.40	7	<5	<10	176	9107	4	347	<10	38	185
170507	1360379	0.054	1	6.24	10	55	3	18	5.65	5	58	73	106	10.51	0.06	38	2.91	1792	<1	98	784	13	1.40	9	<5	<10	185	8712	10	330	<10	30	155
170508	1360380	0.244	1	3.02	429	>5000	2	3	1.22	<4	7	20	30	2.95	<0.01	16	0.44	108	3	10	123	21	1.18	16	8	<10	164	1266	3	21	50	11	18
170509	1360381	0.037	<1	6.57	3	281	2	14	4.63	5	57	72	120	10.31	<0.01	34	2.71	2097	<1	85	915	12	1.83	7	<5	<10	170	8184	8	327	10	37	257
170510D	1360381	0.034	<1	6.28	15	125	3	2	4.76	5	58	74	121	10.38	<0.01	40	2.56	2142	<1	85	900	17	1.97	<5	<5	<10	178	8508	<2	332	<10	31	256
170511	1360382	0.009	2	6.50	16	143	3	<1	6.58	5	55	67	134	11.11	<0.01	39	2.93	2305	<1	71	883	10	1.60	6	<5	<10	179	7564	<2	347	<10	35	404
170512	1360383	0.021	1	6.37	15	78	2	14	6.83	5	45	62	84	9.64	<0.01	40	2.54	2080	<1	72	801	14	1.67	7	6	<10	184	6933	6	300	<10	29	282
170513	1360384	0.015	1	6.00	7	59	3	17	5.70	5	49	69	85	9.89	<0.01	33	2.29	1637	<1	79	888	16	1.56	<5	<5	<10	170	7592	<2	320	<10	28	174
170514	1360385	0.020	<1	5.52	4	100	2	<1	6.32	5	57	74	100	11.08	<0.01	24	2.78	1912	<1	84	964	11	1.65	7	<5	<10	162	8541	6	345	<10	40	182
170515	1360386	0.016	<1	4.54	9	85	2	19	6.55	5	57	75	87	11.05	<0.01	21	2.85	2516	<1	85	875	14	1.44	<5	<5	<10	173	8837	<2	349	<10	37	156
170516	1360387	0.025	1	6.25	8	274	3	18	4.06	6	36	100	122	7.61	<0.01	42	1.71	2338	<1	114	745	20	2.05	6	<5	<10	157	5732	<2	182	11	18	505
170517	1360388	0.079	1	4.96	10	141	2	<1	4.43	6	27	120	63	10.35	<0.01	40	2.21	3598	<1	119	631	26	4.01	<5	<5	<10	134	4133	2	130	12	15	440
170518	1360389	0.110	2	5.74	20	151	3	6	4.26	7	41	83	101	12.98	<0.01	40	2.42	3034	<1	125	536	32	6.99	<5	<5	<10	121	3553	3	134	<10	14	426
170519	1360390	<0.005	<1	3.28	6	327	2	6	2.26	<4	17	53	23	3.60	<0.01	9	1.46	743	<1	30	610	9	0.48	5	<5	<10	243	2843	6	112	16	16	61
170520	1360391	0.044	2	5.31	11	164	2	11	5.32	4	35	80	43	8.89	<0.01	47	2.49	2619	<1	99	549	25	4.64	6	<5	<10	125	3548	6	133	<10	14	395
170521D	1360391	0.057	1	4.86	5	162	3	10	5.45	5	38	84	45	9.30	<0.01	43	2.67	2765	<1	108	562	24	4.71	6	7	<10	115	3646	6	138	11	14	407
170522	1360392	0.084	1	5.30	11	139	2	15	4.68	7	64	84	100	12.82	<0.01	36	2.17	2343	<1	124	516	34	8.39	<5	<5	<10	123	3289	2	125	<10	15	295

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, July 18, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/15/2012
 Date Completed: 06/27/2012
 Job #: 201242109
 Reference: TK 12 248
 Sample #: 252

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
170523	1360393	0.133	2	4.46	2	138	2	25	4.84	6	46	82	75	12.33	<0.01	31	2.35	2581	<1	125	505	26	7.77	7	<5	<10	126	3217	<2	120	<10	13	388
170524	1360394	0.048	<1	6.12	19	159	3	17	5.55	6	28	76	64	10.62	<0.01	34	2.28	2408	<1	111	534	25	6.00	<5	7	<10	146	3338	2	124	<10	15	253
170525	1360395	0.021	1	6.76	4	197	3	9	5.61	4	29	86	28	7.50	<0.01	43	2.11	2379	<1	110	606	20	2.93	<5	<5	<10	167	3843	9	140	<10	14	204
170526	1360396	0.032	1	5.58	6	192	2	15	5.60	4	30	85	27	7.86	<0.01	39	2.26	2450	<1	111	640	24	2.82	<5	<5	<10	155	3879	<2	140	<10	15	224
170527	1360397	0.019	1	5.85	12	182	2	18	5.92	4	31	84	36	7.86	<0.01	37	2.37	2542	<1	108	602	18	2.57	7	<5	11	152	3842	5	143	<10	15	218
170528	1360398	0.025	1	6.65	8	202	3	12	4.82	5	37	91	38	9.30	<0.01	41	2.63	2576	<1	119	643	20	3.19	5	<5	<10	143	4094	<2	152	<10	16	231
170529	1360399	0.031	2	6.27	6	202	3	23	5.97	5	34	85	38	8.20	<0.01	41	2.73	2650	<1	107	599	19	2.41	7	<5	<10	154	3885	<2	145	<10	16	193
170530	1360400	1.724	<1	4.04	15	385	2	19	2.29	<4	18	54	32	3.96	<0.01	11	1.51	777	<1	30	625	11	0.40	5	<5	<10	258	2940	5	121	22	16	60
170531	1360401	0.019	<1	6.20	7	197	3	10	5.76	4	43	79	48	8.02	<0.01	41	2.73	2734	<1	97	593	21	2.27	5	8	10	141	3955	<2	147	10	15	152
170532D	1360401	0.017	1	5.23	7	187	3	13	5.65	4	43	78	49	7.91	<0.01	38	2.68	2702	<1	100	586	15	2.18	6	<5	<10	132	3783	5	144	<10	14	156
170533	1360402	0.015	<1	5.72	<2	202	3	7	5.88	4	37	78	49	7.61	<0.01	47	2.66	2658	<1	99	593	15	1.65	<5	<5	<10	145	4012	4	147	<10	15	157
170534	1360403	0.034	1	4.98	<2	116	2	17	7.80	5	29	65	59	9.93	<0.01	31	2.42	2915	<1	87	508	23	3.39	7	6	<10	136	3378	<2	131	<10	16	190
170535	1360404	0.017	<1	6.45	7	178	3	10	6.24	4	28	79	52	7.88	<0.01	44	2.19	2490	<1	99	579	18	2.02	8	<5	<10	163	3688	3	139	<10	14	162
170536	1360405	0.023	<1	6.28	7	174	2	9	5.55	4	30	77	62	8.34	<0.01	40	2.44	2258	<1	103	609	16	2.53	7	<5	<10	159	3403	<2	135	<10	15	144
170537	1360406	0.045	2	6.32	10	110	3	21	6.93	5	26	69	61	10.38	<0.01	32	2.69	2884	<1	95	541	14	3.16	5	5	<10	139	3215	<2	131	<10	16	164
170538	1360407	0.013	<1	5.76	10	155	2	9	5.85	4	33	80	43	8.02	<0.01	34	2.41	2488	<1	104	632	15	1.83	<5	<5	<10	175	3902	2	146	<10	15	129
170539	1360408	0.014	1	6.04	7	157	2	8	5.25	4	27	72	47	6.98	<0.01	36	2.10	1868	<1	106	618	13	1.92	<5	<5	<10	249	3609	<2	136	<10	14	135
170540	1360409	0.012	<1	4.37	10	245	3	<1	5.20	<4	32	53	47	5.38	<0.01	41	1.77	1609	<1	94	639	10	1.31	6	5	<10	209	3647	3	146	<10	14	88
170541	1360410	<0.005	<1	4.71	9	361	2	4	2.43	<4	17	53	22	3.46	<0.01	13	1.48	721	<1	29	611	10	0.50	<5	<5	<10	271	2987	<2	113	20	17	53
170542	1360411	0.010	<1	4.40	<2	179	2	20	4.06	<4	28	59	49	5.60	<0.01	34	2.24	1649	<1	91	624	13	1.39	<5	5	<10	164	3559	<2	139	<10	14	95

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, July 18, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/15/2012
 Date Completed: 06/27/2012
 Job #: 201242109
 Reference: TK 12 248
 Sample #: 252

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
170543D	1360411	0.010	1	8.88	13	195	2	24	4.57	<4	28	70	53	5.46	<0.01	43	2.30	1637	<1	83	633	12	1.63	14	<5	<10	231	3926	4	144	11	16	137
170544	1360412	0.019	1	6.78	8	111	3	13	5.00	4	46	78	51	7.68	<0.01	36	2.47	2134	<1	112	628	10	3.05	5	5	<10	206	3683	9	132	13	15	148
170545	1360413	0.006	1	6.56	7	188	2	19	5.41	<4	29	88	60	6.24	<0.01	46	2.10	2058	<1	104	623	13	1.13	6	9	<10	215	4056	2	145	<10	13	87
170546	1360414	<0.005	1	7.59	10	223	3	<1	5.83	<4	31	73	58	5.92	0.14	47	2.57	1767	<1	89	622	12	1.16	5	6	<10	187	4059	<2	151	<10	14	106
170547	1360415	0.014	1	7.76	5	180	3	11	5.57	4	31	82	50	7.99	0.08	41	2.42	2608	<1	103	656	12	1.71	5	7	<10	172	4019	<2	149	<10	16	106
170548	1360416	0.006	<1	6.18	8	229	3	21	6.11	<4	33	73	55	6.23	<0.01	42	2.69	1844	<1	90	626	11	1.09	5	<5	<10	177	4041	<2	152	<10	13	100
170549	1360417	0.023	<1	6.26	<2	213	2	15	5.05	4	41	76	70	7.56	<0.01	43	2.46	1918	<1	97	659	10	2.09	6	10	<10	177	4041	4	154	<10	14	127
170550	1360418	0.009	<1	7.78	3	240	3	14	5.01	4	39	78	56	7.86	<0.01	58	2.40	2291	<1	101	606	14	2.27	6	<5	<10	171	3903	<2	143	<10	16	135
170551	1360419	0.026	<1	5.88	5	144	2	22	4.29	7	36	60	74	13.37	<0.01	45	2.52	3553	<1	80	530	20	5.34	5	<5	<10	156	3094	<2	126	<10	15	250
170552	1360420	4.920	67	4.46	39	448	2	<1	1.49	20	14	34	50	3.30	<0.01	12	1.00	569	<1	25	544	573	0.93	51	<5	242	246	1995	11	89	59	14	1770
170553	1360421	0.017	2	7.61	4	186	2	12	4.19	5	24	57	42	9.62	<0.01	52	2.45	2712	<1	62	613	17	2.64	<5	6	<10	201	3485	7	132	10	16	335
170554R	1360421	0.016	<1	6.99	9	180	2	16	4.20	6	22	60	47	9.81	0.20	51	2.49	2683	<1	67	615	14	2.59	7	<5	<10	199	3412	3	133	10	16	293
170555	1360422	0.044	1	7.50	8	104	2	14	4.81	7	34	60	62	13.63	<0.01	43	2.47	3274	<1	85	576	17	6.46	<5	<5	<10	177	3187	<2	122	<10	18	310
170556	1360423	0.036	4	7.05	4	103	3	21	4.39	6	25	59	51	11.39	<0.01	52	2.23	3668	<1	72	602	23	4.43	9	8	<10	172	3615	4	127	10	15	217
170557	1360424	0.041	2	6.12	7	25	3	14	3.63	8	38	58	55	15.38	0.04	34	1.87	3377	<1	72	500	31	9.39	6	<5	<10	219	2750	2	116	<10	14	226
170558	1360425	0.024	1	7.70	9	87	2	19	4.07	7	34	70	30	13.45	<0.01	39	1.90	3254	<1	78	577	29	6.91	5	6	<10	214	3218	<2	129	10	17	221
170559	1360426	0.036	2	7.44	12	82	3	21	4.11	9	27	64	87	16.01	<0.01	44	2.07	4244	<1	87	517	27	9.50	<5	<5	<10	192	3351	3	123	<10	16	236
170560	1360427	0.048	1	6.28	6	70	3	30	3.26	8	30	62	34	15.12	<0.01	26	1.77	2507	<1	76	416	30	>10.00	<5	<5	<10	200	2952	4	116	<10	14	245
170561	1360428	0.065	2	6.37	14	13	3	20	2.53	11	47	66	107	20.27	<0.01	34	1.41	1806	<1	135	429	44	>10.00	<5	<5	<10	146	2758	<2	103	<10	12	291
170562	1360429	0.088	3	5.37	18	49	4	32	2.19	12	67	54	181	22.13	<0.01	30	1.18	1591	<1	129	378	47	>10.00	6	<5	<10	125	2191	6	87	<10	10	273

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, July 18, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/15/2012
 Date Completed: 06/27/2012
 Job #: 201242109
 Reference: TK 12 248
 Sample #: 252

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
170563	1360430	0.006	<1	7.68	12	401	2	15	2.61	<4	17	53	23	3.58	<0.01	20	1.55	706	<1	29	612	11	0.93	6	7	<10	309	3054	3	113	24	18	50
170564	1360431	0.006	<1	8.05	7	311	2	15	3.68	<4	41	344	24	4.17	<0.01	48	1.28	1345	<1	116	728	13	1.05	5	<5	<10	226	4672	4	119	<10	15	636
170565D	1360431	<0.005	<1	7.29	14	302	3	14	3.62	<4	42	350	25	4.21	<0.01	45	1.26	1333	<1	124	736	13	0.99	10	<5	<10	220	4467	<2	118	11	15	650
170566	1360432	<0.005	<1	6.82	8	218	2	6	4.20	<4	41	297	27	4.89	<0.01	48	1.78	1510	<1	137	629	6	0.84	5	6	11	191	3947	7	103	12	14	171
170567	1360433	0.019	<1	5.29	56	71	2	16	3.38	5	23	72	46	9.78	<0.01	26	1.94	2809	<1	127	633	11	1.74	7	<5	<10	122	2710	2	68	<10	19	146
170568	1360434	0.009	<1	6.00	14	196	2	10	3.26	<4	27	160	34	4.69	<0.01	34	1.86	1306	<1	100	813	12	0.59	<5	5	<10	154	4039	3	83	<10	14	96
170569	1360435	0.011	<1	6.06	28	203	2	6	3.10	<4	27	104	49	6.70	<0.01	32	1.91	1975	<1	136	669	10	1.23	<5	<5	<10	129	3722	<2	82	<10	15	126
170570	1360436	0.012	1	6.57	46	223	3	8	3.19	<4	30	105	37	6.09	<0.01	37	1.81	1858	<1	133	652	7	1.18	6	<5	<10	143	3803	<2	83	<10	14	108
170571	1360437	0.030	<1	6.24	8	244	3	21	4.39	<4	36	60	66	6.40	<0.01	28	1.78	1492	<1	61	728	17	1.39	7	<5	<10	154	5560	6	217	<10	26	163
170572	1360438	0.021	<1	6.10	10	20	3	18	6.44	5	55	65	130	10.41	<0.01	22	2.21	2242	<1	63	963	16	0.79	6	<5	<10	215	8337	4	339	14	40	175
170573	1360439	0.011	<1	5.21	<2	37	3	8	5.97	5	49	62	73	9.95	<0.01	21	2.06	2257	<1	62	965	18	0.71	<5	<5	<10	198	6213	3	330	<10	39	125
170574	1360440	0.240	<1	1.71	448	>5000	2	16	1.10	<4	7	19	30	3.00	<0.01	11	0.36	106	2	11	116	22	0.99	18	7	<10	145	1133	9	20	54	10	20
170575	1360441	0.129	1	8.18	12	208	3	28	5.86	5	50	63	71	10.50	<0.01	36	2.24	2473	<1	68	965	17	1.19	<5	6	<10	198	7372	4	350	10	42	160
170576D	1360441	0.190	<1	7.49	4	78	3	<1	5.67	5	48	61	70	10.20	<0.01	34	2.17	2409	<1	63	934	22	1.14	<5	11	<10	190	7193	3	340	<10	41	152
170577	1360442	2.174	<1	4.15	8	116	2	25	4.04	5	47	66	73	10.18	<0.01	27	2.18	2846	<1	79	904	21	1.68	6	<5	<10	193	4742	2	310	<10	33	330
170578	1360443	0.051	1	4.93	9	162	2	9	5.36	5	47	71	83	9.67	<0.01	29	2.15	2017	<1	82	892	19	0.98	5	<5	<10	168	5655	<2	322	<10	38	135
170579	1360444	0.217	1	6.94	4	135	3	5	5.21	5	47	68	95	10.14	<0.01	44	2.33	2178	<1	69	854	24	1.44	6	<5	<10	202	7170	<2	316	<10	38	135
170580	1360445	<0.005	1	7.32	6	103	3	9	5.57	5	53	70	71	10.42	<0.01	35	2.17	2103	<1	75	933	12	0.83	7	8	<10	214	9173	<2	334	<10	41	124
170581	1360446	0.019	1	6.95	4	92	2	22	5.56	5	56	65	130	10.32	<0.01	40	2.30	2268	<1	72	921	12	1.14	5	<5	<10	188	8820	2	331	10	39	159
170582	1360447	0.105	1	6.47	8	371	3	11	4.72	4	55	81	130	7.95	<0.01	52	2.33	2253	<1	106	980	15	1.53	<5	<5	<10	185	9125	3	340	12	38	297

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, July 18, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/15/2012
 Date Completed: 06/27/2012
 Job #: 201242109
 Reference: TK 12 248
 Sample #: 252

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
170583	1360448	0.128	<1	6.69	9	193	3	15	4.79	5	54	69	92	8.73	<0.01	50	2.04	2376	<1	74	986	15	1.14	7	<5	<10	185	9166	5	349	<10	39	135
170584	1360449	1.454	2	6.35	3	171	3	21	3.26	11	50	67	215	9.07	<0.01	47	2.01	1480	<1	79	835	26	3.59	6	7	<10	158	6132	5	300	27	24	1902
170585	1360450	<0.005	<1	6.22	8	393	2	2	2.53	<4	16	52	24	3.44	<0.01	16	1.51	700	<1	28	603	4	0.61	5	5	<10	299	2994	<2	116	23	17	74
170586	1360451	0.084	1	5.76	10	192	2	5	2.84	5	41	55	110	8.17	<0.01	51	2.09	1462	<1	61	764	13	3.05	7	11	<10	141	5323	6	249	13	27	452
170587D	1360451	0.069	1	6.47	14	198	3	7	3.00	5	42	58	115	8.48	<0.01	55	2.18	1530	<1	64	783	15	3.19	8	<5	<10	146	5677	<2	260	<10	28	462
170588	1360452	0.258	2	6.73	8	201	2	12	2.74	10	32	63	141	4.40	<0.01	41	1.51	996	<1	84	726	16	2.07	<5	<5	<10	151	4401	<2	188	30	19	2073
170589	1360453	0.284	2	6.26	6	96	2	14	3.06	7	45	75	219	9.68	<0.01	44	2.47	1536	<1	89	848	14	3.76	<5	<5	<10	144	4759	3	276	23	25	746
170590	1360454	0.126	1	5.74	<2	72	2	8	4.50	6	48	58	181	9.54	<0.01	44	3.32	2262	<1	65	965	17	2.09	<5	<5	<10	153	4912	7	343	14	36	499
170591	1360455	0.372	1	6.50	3	106	3	11	3.94	5	46	48	105	9.04	<0.01	48	2.66	1790	<1	53	1076	16	1.92	<5	<5	<10	140	6658	<2	356	11	40	191
170592	1360456	0.502	1	9.04	12	114	2	2	4.12	5	49	50	105	9.46	<0.01	57	2.76	1908	<1	57	1094	16	2.09	<5	10	<10	156	8891	<2	371	13	42	190
170593	1360457	0.020	1	7.29	7	150	3	14	4.73	4	39	60	70	8.07	<0.01	41	1.97	1768	<1	72	940	12	1.19	6	6	<10	167	6986	9	289	<10	33	134
170594	1360458	0.126	2	9.00	2	93	2	8	5.86	6	52	67	138	10.64	<0.01	45	2.98	2065	<1	58	975	18	1.74	<5	10	<10	191	7849	6	351	15	42	163
170595	1360459	0.185	1	6.40	<2	81	3	13	6.23	6	51	62	114	11.39	<0.01	30	2.28	2616	<1	65	925	17	1.59	5	<5	<10	156	5872	<2	330	<10	40	144
170596	1360460	1.791	<1	9.56	10	438	2	10	2.79	<4	19	55	32	3.90	<0.01	28	1.69	769	<1	32	650	14	0.89	6	<5	<10	317	3242	3	124	30	20	56
170597	1360461	0.027	1	8.95	7	149	3	7	6.16	5	53	67	66	10.68	<0.01	44	2.27	2566	<1	75	955	16	1.03	<5	<5	<10	198	7953	4	338	<10	40	131
170598D	1360461	0.017	1	8.20	7	136	3	18	5.75	5	49	62	62	10.00	<0.01	42	2.10	2422	<1	67	883	21	1.02	<5	<5	<10	187	7531	4	319	<10	37	127
170599	1360462	0.229	1	7.60	<2	161	3	4	5.82	4	48	62	105	8.73	<0.01	49	2.21	2233	<1	63	836	18	2.67	7	<5	<10	186	8280	4	303	19	32	94
170600	1360463	0.111	2	6.93	16	148	2	<1	4.37	14	51	64	99	10.03	<0.01	46	2.36	2252	<1	69	798	18	3.27	5	<5	<10	146	6681	2	296	26	27	1135
170601	1360464	12.438	2	6.98	4	278	3	29	3.55	4	47	76	92	8.06	<0.01	43	1.97	1432	<1	75	843	23	2.95	<5	<5	<10	171	6674	9	319	<10	23	190
170602	1360465	0.089	<1	6.45	6	255	3	16	5.14	5	51	71	96	9.08	<0.01	41	2.47	1724	<1	63	960	15	1.80	<5	<5	<10	194	7756	2	340	10	39	155

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, July 18, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/15/2012
 Date Completed: 06/27/2012
 Job #: 201242109
 Reference: TK 12 248
 Sample #: 252

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
170603	1360466	0.083	<1	5.04	12	107	2	9	4.68	5	49	76	95	10.43	<0.01	25	2.98	1752	<1	63	999	13	1.27	<5	<5	<10	161	5685	<2	356	<10	40	198
170604	1360467	0.254	1	6.18	<2	122	2	4	5.45	6	50	76	137	10.09	<0.01	29	3.14	2027	<1	68	997	14	1.98	<5	5	<10	179	6680	5	342	<10	39	322
170605	1360468	0.498	1	6.40	9	108	3	4	5.20	6	49	86	128	10.35	<0.01	28	2.84	2072	<1	83	974	18	2.16	6	<5	<10	188	6671	5	340	12	40	249
170606	1360469	0.043	1	7.68	<2	195	3	33	5.18	5	51	77	107	10.08	<0.01	37	3.00	1891	<1	70	945	20	2.09	7	<5	<10	192	7128	<2	336	10	39	226
170607	1360470	<0.005	<1	5.66	6	400	2	11	2.57	<4	17	54	23	3.55	<0.01	14	1.54	728	<1	28	619	8	0.54	6	6	<10	301	3041	6	119	23	18	54
170608	1360471	0.423	1	7.71	10	172	2	20	5.26	5	50	74	109	9.98	<0.01	34	2.78	1761	<1	65	949	28	2.24	8	<5	<10	201	6266	3	337	14	38	246
170609D	1360471	0.356	<1	5.60	5	169	3	7	5.34	6	52	76	111	10.42	<0.01	28	2.84	1755	<1	69	1000	23	2.18	6	<5	<10	195	5253	<2	354	10	38	233
170610	1360472	0.479	<1	7.79	3	147	3	22	5.03	8	52	76	113	10.40	<0.01	36	2.92	1814	<1	67	976	19	1.90	7	<5	<10	186	6014	<2	340	11	40	801
170611	1360473	0.298	<1	4.85	<2	189	2	12	3.56	6	44	78	86	8.53	<0.01	32	2.46	1656	<1	80	950	15	2.44	<5	<5	<10	121	4931	4	281	34	27	338
170612	1360474	0.015	<1	8.79	13	347	3	<1	3.33	<4	10	51	9	2.60	<0.01	32	1.58	1070	<1	72	515	15	1.07	5	5	<10	175	1797	<2	50	<10	11	78
170613	1360475	0.093	1	7.48	13	172	2	4	3.85	5	41	74	124	8.60	<0.01	42	2.58	1767	<1	91	927	23	1.67	7	<5	<10	149	5226	6	237	12	32	170
170614	1360476	0.100	<1	5.07	<2	160	2	12	3.53	5	40	68	129	8.50	<0.01	36	2.47	1664	<1	92	936	19	1.47	9	<5	<10	135	4426	9	231	10	30	183
170615	1360477	0.139	<1	4.57	4	113	3	23	4.42	5	44	66	135	10.45	<0.01	31	2.96	2560	<1	80	818	17	1.28	<5	<5	<10	126	4353	<2	300	<10	34	245
170616	1360478	0.247	16	6.77	5	90	2	28	4.80	5	44	69	101	10.52	<0.01	30	2.44	2564	<1	81	684	14	1.47	7	<5	<10	144	5399	<2	280	<10	37	124
170617	1360479	0.081	1	6.54	8	136	3	<1	4.54	5	49	82	129	9.88	<0.01	30	2.47	2522	<1	103	825	9	1.23	5	<5	<10	144	5635	4	310	12	35	223
170618	1360480	4.869	68	6.13	49	447	2	11	1.61	18	15	33	51	3.18	<0.01	17	1.04	529	<1	22	551	545	1.04	53	<5	228	252	2099	4	90	60	16	1666
170619	1360481	0.017	1	6.31	8	184	2	14	4.81	4	48	80	116	8.55	<0.01	28	1.88	2120	<1	81	804	17	0.80	<5	<5	<10	170	6251	<2	315	<10	32	125
170620R	1360481	0.012	1	8.81	18	202	3	19	5.03	4	49	74	114	8.82	<0.01	37	2.01	2265	<1	63	820	12	1.00	6	<5	<10	185	7178	<2	330	<10	35	108
170621	1360482	0.028	1	8.33	<2	221	3	22	5.58	5	57	75	113	9.66	<0.01	35	2.46	2292	<1	70	815	14	1.16	8	<5	<10	192	6858	8	347	12	40	109
170622	1360483	0.017	<1	7.12	4	106	3	3	5.01	6	55	69	112	10.40	<0.01	25	2.45	2112	<1	67	788	12	1.22	6	<5	<10	172	6345	3	335	<10	38	132

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, July 18, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 06/15/2012
 Date Completed: 06/27/2012
 Job #: 201242109
 Reference: TK 12 248
 Sample #: 252

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
170623	1360484	0.030	<1	7.06	6	756	3	21	6.95	<4	17	34	31	4.19	<0.01	19	2.15	1782	<1	50	586	25	1.68	<5	<5	<10	389	3603	<2	128	10	28	90
170624	1360485	0.020	<1	6.86	8	301	2	12	4.03	<4	10	43	10	2.45	<0.01	16	1.81	919	<1	77	559	18	0.98	<5	10	<10	210	2047	3	46	<10	9	44
170625	1360486	0.019	<1	9.34	14	302	2	12	3.03	<4	11	33	11	2.19	<0.01	30	1.62	688	<1	50	565	12	1.32	6	7	<10	190	1941	<2	38	<10	10	28
170626	1360487	0.021	<1	9.04	19	399	3	11	2.78	<4	9	48	7	2.20	<0.01	34	1.57	738	<1	76	557	10	1.36	5	9	<10	203	1869	2	39	<10	9	41
170627	1360488	0.030	<1	7.04	13	446	3	7	2.55	<4	16	49	32	2.12	<0.01	27	1.34	645	<1	81	544	13	1.27	6	5	<10	204	1541	4	37	10	8	58
170628	1360489	0.020	<1	9.01	7	339	2	13	2.52	<4	9	38	6	1.84	<0.01	34	1.36	570	<1	59	535	13	1.14	5	5	<10	185	1727	<2	39	<10	9	30
170629	1360490	0.012	<1	6.75	11	386	2	5	2.49	<4	15	49	20	3.19	<0.01	18	1.48	662	<1	27	583	7	0.68	6	<5	<10	297	2848	<2	108	21	17	46
170630	1360491	0.015	<1	6.39	11	233	2	12	2.43	<4	7	57	5	2.00	<0.01	26	1.18	503	1	91	553	6	0.95	<5	<5	<10	178	1522	<2	40	<10	8	44
170631D	1360491	0.015	<1	6.29	12	228	2	5	2.41	<4	6	57	4	1.91	<0.01	29	1.08	482	2	92	512	9	1.07	<5	8	<10	179	1481	4	38	<10	7	44
170632	1360492	0.011	<1	7.48	7	282	2	21	2.39	<4	7	33	3	1.76	<0.01	29	1.05	386	<1	49	527	10	0.97	<5	11	<10	176	1523	<2	35	<10	8	18
170633	1360493	0.046	<1	6.70	<2	305	2	<1	2.06	<4	8	30	7	1.86	0.10	26	1.09	386	<1	48	563	8	0.76	<5	6	<10	161	1637	<2	38	<10	7	21
170634	1360494	0.019	<1	7.81	6	370	2	5	2.95	<4	8	40	5	2.27	<0.01	33	1.61	620	<1	66	535	7	0.94	<5	5	<10	188	1778	4	35	<10	8	30
170635	1360495	0.017	<1	5.40	3	300	2	10	1.95	<4	10	33	22	2.09	<0.01	23	1.23	457	<1	52	551	10	0.85	<5	<5	<10	148	1667	2	35	<10	7	17
170636	1360496	0.017	<1	8.82	10	354	2	14	2.34	<4	10	35	24	2.10	<0.01	31	1.24	421	<1	59	557	8	1.07	<5	6	<10	191	1771	3	37	<10	9	20
170637	1360497	0.009	<1	8.42	<2	322	2	12	1.90	<4	9	41	14	1.88	<0.01	29	1.09	353	<1	68	571	11	0.92	<5	11	<10	180	1979	<2	39	<10	8	16
170638	1360498	<0.005	<1	7.47	8	282	2	15	2.21	<4	8	49	4	1.96	<0.01	25	1.12	430	<1	84	544	9	0.76	<5	5	<10	192	1676	2	37	<10	8	20
170639	1360499	<0.005	<1	8.04	12	254	2	6	2.41	<4	6	30	3	1.88	<0.01	25	1.14	435	<1	48	549	10	0.83	<5	6	<10	191	1700	5	36	<10	8	19
170640	1360500	0.230	<1	3.02	441	>5000	<2	9	1.15	<4	6	18	29	2.83	<0.01	15	0.40	<100	2	11	117	24	1.21	15	8	<10	147	939	8	16	49	11	17
170641	1360501	0.006	<1	8.07	13	420	2	9	2.51	<4	9	34	5	2.19	<0.01	28	1.05	389	<1	53	541	9	0.90	<5	6	<10	198	2127	5	51	<10	9	29
170642D	1360501	0.005	<1	8.29	5	273	2	11	2.60	<4	9	34	5	2.26	<0.01	29	1.08	408	<1	50	579	9	0.89	<5	8	<10	203	2207	3	53	<10	9	30

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, July 18, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/15/2012
 Date Completed: 06/27/2012
 Job #: 201242109
 Reference: TK 12 248
 Sample #: 252

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
170643	1360502	0.007	<1	7.29	4	295	2	16	2.43	<4	8	35	3	1.99	<0.01	24	1.00	359	<1	56	558	7	0.85	<5	9	<10	189	1807	<2	39	<10	7	21
170644	1360503	<0.005	<1	9.68	4	319	3	20	2.53	<4	8	32	5	2.00	<0.01	28	1.17	406	<1	53	581	7	1.03	<5	5	<10	193	1769	<2	39	<10	9	22
170645	1360504	0.007	<1	8.85	5	302	2	6	2.32	<4	8	36	6	1.97	<0.01	25	1.13	349	<1	60	573	12	1.08	<5	8	<10	163	1607	<2	38	<10	9	23
170646	1360505	<0.005	<1	9.28	11	302	2	19	2.51	<4	10	46	10	2.09	<0.01	25	1.12	379	<1	76	568	10	1.14	<5	10	<10	168	1685	6	39	<10	9	23
170647	1360506	0.005	<1	7.94	3	321	2	9	2.56	<4	10	50	7	2.15	<0.01	22	1.20	510	1	84	549	8	1.03	<5	10	<10	182	1927	<2	37	<10	8	19
170648	1360507	0.009	<1	8.09	8	319	2	6	2.78	<4	11	45	7	2.30	<0.01	22	1.34	686	<1	79	547	12	1.16	5	7	<10	170	2094	2	39	<10	8	20
170649	1360508	0.016	<1	9.99	10	354	2	5	2.65	<4	10	49	60	2.34	<0.01	26	1.31	647	1	88	594	14	1.43	<5	7	<10	168	2255	<2	42	<10	10	211
170650	1360509	0.020	<1	8.54	8	332	2	10	2.26	<4	14	85	13	3.03	<0.01	21	1.29	660	3	78	526	38	2.21	<5	7	<10	132	1931	<2	50	<10	12	45
170651	1360510	0.006	<1	6.44	13	380	2	<1	2.43	<4	15	50	20	3.17	<0.01	16	1.46	657	<1	27	581	8	0.63	<5	8	<10	290	2880	5	107	21	17	47
170652	1360511	0.035	1	5.62	148	300	3	12	1.89	<4	17	64	61	4.79	<0.01	13	1.13	708	6	110	478	33	3.38	<5	6	<10	108	1701	4	41	10	9	218
170653D	1360511	0.035	1	6.70	141	314	3	9	1.99	<4	17	67	62	4.86	<0.01	18	1.16	722	6	122	480	36	3.52	7	<5	<10	115	1754	<2	41	12	9	224
170654	1360512	0.053	2	5.73	1915	221	3	16	1.41	5	38	57	142	7.64	<0.01	18	1.14	562	2	114	395	25	5.55	<5	6	<10	90	1545	6	44	<10	10	373
170655	1360513	0.033	1	7.04	332	303	2	17	1.92	<4	13	46	33	3.21	<0.01	18	1.21	472	<1	80	517	26	2.34	6	8	<10	132	1939	3	39	<10	8	187
170656	1360514	0.010	<1	8.71	39	316	3	16	1.85	<4	11	103	29	2.85	<0.01	24	1.20	456	<1	93	525	25	2.16	<5	<5	10	133	1951	<2	57	10	12	72
170657	1360515	0.012	<1	7.16	125	281	2	21	2.81	<4	16	163	37	2.99	<0.01	19	1.50	770	3	138	463	18	2.10	<5	6	<10	135	1608	<2	69	<10	14	61
170658	1360516	0.012	1	6.60	140	267	3	8	2.52	<4	15	143	35	2.68	<0.01	18	1.36	680	<1	102	441	17	1.86	<5	6	<10	129	1547	2	66	<10	12	61
170659	1360517	0.037	<1	5.28	10	248	3	2	2.13	<4	18	137	44	3.49	<0.01	14	1.37	716	<1	83	452	17	1.81	<5	<5	<10	114	2148	<2	63	<10	13	49
170660	1360518	0.055	<1	6.16	5	269	2	23	3.39	<4	17	141	40	3.49	<0.01	16	1.80	985	<1	97	442	18	2.38	5	6	<10	144	1589	<2	63	<10	14	37
170661	1360519	0.024	<1	3.00	4	205	2	12	1.90	<4	11	142	31	2.90	<0.01	8	1.22	741	6	142	348	16	1.89	5	<5	<10	109	1223	<2	49	<10	11	33
170662	1360520	1.864	<1	6.36	12	411	2	10	2.40	<4	17	53	30	3.62	<0.01	17	1.52	710	<1	29	611	11	0.64	5	6	<10	286	2910	5	116	25	17	57

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, July 18, 2012

Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/15/2012
 Date Completed: 06/27/2012
 Job #: 201242109
 Reference: TK 12 248
 Sample #: 252

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
170663	1360521	0.101	1	8.59	11	481	3	27	2.73	<4	19	154	41	3.76	<0.01	25	1.49	870	<1	105	615	25	2.87	6	6	<10	191	2007	<2	92	<10	17	52
170664D	1360521	0.124	1	8.97	12	480	3	22	2.76	<4	19	148	40	3.71	<0.01	25	1.54	878	<1	97	612	29	2.82	<5	<5	<10	190	1982	3	91	<10	18	50
170665	1360522	0.021	<1	3.84	6	271	3	9	1.72	<4	18	148	43	3.49	<0.01	15	1.32	548	<1	108	466	15	1.83	5	11	<10	131	2024	6	63	<10	14	47
170666	1360523	0.047	<1	5.43	9	294	2	6	2.93	<4	18	135	40	3.63	<0.01	17	1.67	828	<1	88	431	19	2.25	<5	8	<10	159	1964	<2	64	<10	14	255
170667	1360524	0.024	<1	5.72	9	296	3	7	2.95	<4	17	135	32	3.31	<0.01	21	1.47	856	<1	83	448	13	2.34	7	10	<10	156	1738	7	61	<10	11	49
170668	1360525	0.017	<1	7.93	8	356	3	6	2.84	<4	9	33	5	2.21	<0.01	23	1.54	740	<1	50	556	21	1.48	5	7	<10	170	1807	<2	38	<10	9	13
170669	1360526	0.015	<1	6.45	11	320	2	6	3.17	<4	9	19	2	2.22	<0.01	19	1.64	832	<1	30	542	13	1.54	6	<5	<10	160	1542	<2	34	<10	9	20
170670	1360527	0.008	<1	8.69	5	424	2	11	3.03	<4	8	25	3	2.12	<0.01	27	1.39	683	<1	37	550	17	1.72	<5	6	<10	193	1832	4	37	<10	8	27
170671	1360528	0.009	<1	6.44	9	372	2	20	2.46	<4	9	25	8	2.13	<0.01	24	1.31	656	<1	39	555	17	1.54	<5	10	<10	163	1706	<2	35	<10	7	43
170672	1360529	0.009	<1	6.63	3	374	3	9	2.50	<4	9	26	7	2.25	<0.01	26	1.31	681	<1	44	584	16	1.71	8	<5	<10	169	1755	<2	37	<10	7	29
170673	1360530	<0.005	<1	5.17	11	383	2	12	2.37	<4	16	51	28	3.30	<0.01	12	1.43	671	<1	25	575	4	0.52	9	5	<10	287	2850	<2	109	20	16	103
170674	1360531	0.095	2	4.33	21	145	3	24	1.71	7	33	34	205	10.36	<0.01	21	0.86	555	<1	67	355	42	7.80	<5	7	<10	95	1335	<2	47	16	9	995
170675D	1360531	0.100	3	7.85	19	3	3	16	2.41	10	41	56	262	13.01	<0.01	35	1.09	695	<1	111	459	52	9.95	8	11	10	117	1673	<2	58	26	12	1238
170676	1360532	0.189	3	4.84	15	21	4	37	2.54	13	45	70	343	19.58	<0.01	28	2.05	1866	<1	162	366	83	>10.00	<5	<5	<10	112	2284	<2	119	14	26	936
170677	1360533	0.036	<1	8.69	74	189	3	15	5.97	6	64	58	89	12.45	<0.01	43	2.47	3298	<1	82	1030	27	1.56	<5	<5	<10	250	8508	11	448	10	45	362
170678	1360534	0.005	<1	5.65	11	210	3	7	5.66	6	51	49	124	11.63	<0.01	42	2.18	3295	<1	83	807	19	1.76	6	<5	<10	251	6887	<2	305	<10	41	175
170679	1360535	0.014	<1	7.60	6	113	3	10	6.70	6	68	46	203	12.46	<0.01	40	2.26	3129	<1	77	994	15	1.15	<5	6	<10	262	8345	<2	406	<10	49	147
170680	1360536	<0.005	1	8.85	2	123	3	3	6.32	6	65	43	162	11.65	<0.01	48	2.19	2896	<1	69	948	12	1.28	5	<5	<10	258	8242	<2	384	<10	48	133
170681	1360537	<0.005	<1	7.34	11	128	3	25	5.47	6	66	44	141	11.38	<0.01	35	2.02	2657	<1	81	1002	10	1.06	<5	<5	<10	256	6320	2	395	11	49	142
170682	1360538	0.007	<1	6.54	15	144	3	15	5.60	5	59	51	129	10.81	<0.01	30	1.95	2472	<1	92	810	10	1.05	6	<5	<10	216	5564	6	371	<10	46	141

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, July 18, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/15/2012
 Date Completed: 06/27/2012
 Job #: 201242109
 Reference: TK 12 248
 Sample #: 252

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
170683	1360539	<0.005	<1	5.47	11	67	3	10	4.08	5	55	44	119	9.59	<0.01	30	1.76	2364	<1	78	909	9	0.84	<5	<5	<10	191	5708	4	353	<10	42	105
170684	1360540	4.977	71	4.01	41	429	2	19	1.42	19	14	32	51	3.17	<0.01	11	0.95	529	<1	23	527	565	0.87	50	<5	231	239	1976	<2	90	57	14	1693
170685	1360541	0.008	2	6.10	5	86	3	11	5.01	5	54	45	120	10.46	0.14	22	1.95	2846	<1	58	876	22	0.76	5	<5	10	201	6602	2	349	<10	42	169
170686R	1360541	0.006	<1	4.33	4	66	2	16	4.70	5	53	47	121	10.23	0.09	20	1.76	2749	<1	61	795	5	0.74	5	<5	<10	185	6187	<2	340	<10	36	132
170687	1360542	0.009	<1	4.29	10	136	3	14	4.72	4	54	63	91	9.19	<0.01	22	1.59	2130	<1	75	722	13	0.68	7	9	<10	205	5547	<2	329	<10	33	129
170688	1360543	0.023	<1	5.13	10	37	2	3	4.86	5	55	55	121	9.61	<0.01	20	1.93	1728	<1	66	714	9	0.81	5	<5	<10	193	5720	2	309	<10	37	122
170689	1360544	0.008	<1	5.09	10	28	2	17	5.06	5	53	64	107	9.82	0.07	20	1.82	2167	<1	66	792	8	0.65	<5	<5	<10	184	5626	7	341	<10	38	126
170690	1360545	<0.005	<1	5.19	12	44	2	13	4.83	5	63	69	120	9.18	<0.01	23	1.70	2285	<1	88	757	6	0.98	6	<5	<10	154	4137	6	328	<10	37	123
170691	1360546	0.009	<1	5.24	8	49	3	19	4.35	4	61	68	99	8.69	<0.01	24	1.66	2142	<1	79	760	9	0.75	<5	10	<10	152	5232	3	327	13	37	143
170692	1360547	0.006	<1	5.73	8	86	3	9	5.06	5	59	80	124	9.25	<0.01	30	1.73	2583	<1	98	818	14	0.75	7	<5	<10	177	5606	6	340	<10	38	150
170693	1360548	0.021	<1	6.24	<2	80	2	10	3.72	4	52	73	135	7.99	<0.01	37	1.46	2359	<1	69	798	9	0.85	<5	<5	<10	184	5209	2	349	<10	36	118
170694	1360549	0.010	<1	4.79	5	109	3	21	4.82	4	55	70	180	9.19	<0.01	25	1.74	2036	<1	71	786	5	0.69	<5	<5	<10	177	5959	<2	333	<10	37	117
170695	1360550	<0.005	<1	3.25	15	345	3	<1	2.11	<4	16	47	20	3.12	<0.01	7	1.33	631	<1	25	557	5	0.38	<5	<5	<10	258	2482	2	104	18	15	50
170696	1360551	<0.005	<1	2.84	<2	91	2	11	4.62	4	49	71	105	8.56	<0.01	20	1.71	1724	<1	78	737	8	0.51	6	<5	<10	171	4016	6	312	<10	35	112
170697D	1360551	0.006	<1	3.53	3	100	2	12	4.79	5	52	70	107	8.84	0.04	22	1.75	1898	<1	77	737	7	0.53	<5	9	<10	184	5598	<2	318	<10	36	116
170698	1360552	0.009	<1	4.31	5	88	2	14	5.24	5	53	68	64	9.51	0.03	17	1.81	2030	<1	71	758	8	0.49	<5	<5	<10	169	6068	<2	317	<10	37	128
170699	1360553	0.005	<1	4.32	4	78	2	14	5.23	5	53	64	98	9.21	<0.01	16	1.85	2081	<1	64	723	4	0.53	<5	<5	<10	188	6047	5	318	<10	35	117

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, June 27, 2012

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/15/2012
 Date Completed: 06/27/2012
 Job #: 201242109
 Reference: TK 12 248
 Sample #: 252

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
170423	1360302	8	<0.001	0.008
170424	1360303	16	<0.001	0.016
170425	1360304	<5	<0.001	<0.005
170426	1360305	<5	<0.001	<0.005
170427	1360306	19	<0.001	0.019
170428	1360307	17	<0.001	0.017
170429	1360308	32	<0.001	0.032
170430	1360309	8	<0.001	0.008
170431	1360310	8	<0.001	0.008
170432	1360311	9	<0.001	0.009
170433 Dup	1360311	17	<0.001	0.017
170434	1360312	68	0.002	0.068
170435	1360313	23	<0.001	0.023
170436	1360314	69	0.002	0.069
170437	1360315	29	<0.001	0.029
170438	1360316	14	<0.001	0.014
170439	1360317	11	<0.001	0.011
170440	1360318	11	<0.001	0.011
170441	1360319	9	<0.001	0.009
170442	1360320	242	0.007	0.242
170443	1360321	<5	<0.001	<0.005
170444 Dup	1360321	<5	<0.001	<0.005
170445	1360322	30	<0.001	0.030
170446	1360323	9	<0.001	0.009
170447	1360324	25	<0.001	0.025
170448	1360325	11	<0.001	0.011
170449	1360326	10	<0.001	0.010
170450	1360327	26	<0.001	0.026
170451	1360328	28	<0.001	0.028
170452	1360329	19	<0.001	0.019

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, June 27, 2012

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/15/2012
 Date Completed: 06/27/2012
 Job #: 201242109
 Reference: TK 12 248
 Sample #: 252

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
170453	1360330	<5	<0.001	<0.005
170454	1360331	66	0.002	0.066
170455 Dup	1360331	19	<0.001	0.019
170456	1360332	14	<0.001	0.014
170457	1360333	20	<0.001	0.020
170458	1360334	35	0.001	0.035
170459	1360335	162	0.005	0.162
170460	1360336	105	0.003	0.105
170461	1360337	14	<0.001	0.014
170462	1360338	13	<0.001	0.013
170463	1360339	40	0.001	0.040
170464	1360340	1761	0.051	1.761
170465	1360341	7	<0.001	0.007
170466 Dup	1360341	13	<0.001	0.013
170467	1360342	15	<0.001	0.015
170468	1360343	11	<0.001	0.011
170469	1360344	12	<0.001	0.012
170470	1360345	19	<0.001	0.019
170471	1360346	34	0.001	0.034
170472	1360347	149	0.004	0.149
170473	1360348	14	<0.001	0.014
170474	1360349	12	<0.001	0.012
170475	1360350	<5	<0.001	<0.005
170476	1360351	24	<0.001	0.024
170477 Dup	1360351	28	<0.001	0.028
170478	1360352	22	<0.001	0.022
170479	1360353	5	<0.001	0.005
170480	1360354	<5	<0.001	<0.005
170481	1360355	22	<0.001	0.022
170482	1360356	18	<0.001	0.018

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, June 27, 2012

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/15/2012
 Date Completed: 06/27/2012
 Job #: 201242109
 Reference: TK 12 248
 Sample #: 252

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
170483	1360357	<5	<0.001	<0.005
170484	1360358	10	<0.001	0.010
170485	1360359	14	<0.001	0.014
170486	1360360	4730	0.138	4.730
170487	1360361	25	<0.001	0.025
170488 Rep	1360361	11	<0.001	0.011
170489	1360362	35	0.001	0.035
170490	1360363	8	<0.001	0.008
170491	1360364	26	<0.001	0.026
170492	1360365	28	<0.001	0.028
170493	1360366	7	<0.001	0.007
170494	1360367	<5	<0.001	<0.005
170495	1360368	<5	<0.001	<0.005
170496	1360369	<5	<0.001	<0.005
170497	1360370	<5	<0.001	<0.005
170498	1360371	8	<0.001	0.008
170499 Dup	1360371	5	<0.001	0.005
170500	1360372	7	<0.001	0.007
170501	1360373	<5	<0.001	<0.005
170502	1360374	10	<0.001	0.010
170503	1360375	20	<0.001	0.020
170504	1360376	32	<0.001	0.032
170505	1360377	5	<0.001	0.005
170506	1360378	13	<0.001	0.013
170507	1360379	54	0.002	0.054
170508	1360380	244	0.007	0.244
170509	1360381	37	0.001	0.037
170510 Dup	1360381	34	<0.001	0.034
170511	1360382	9	<0.001	0.009
170512	1360383	21	<0.001	0.021

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.

The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, June 27, 2012

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/15/2012
 Date Completed: 06/27/2012
 Job #: 201242109
 Reference: TK 12 248
 Sample #: 252

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
170513	1360384	15	<0.001	0.015
170514	1360385	20	<0.001	0.020
170515	1360386	16	<0.001	0.016
170516	1360387	25	<0.001	0.025
170517	1360388	79	0.002	0.079
170518	1360389	110	0.003	0.110
170519	1360390	<5	<0.001	<0.005
170520	1360391	44	0.001	0.044
170521 Dup	1360391	57	0.002	0.057
170522	1360392	84	0.002	0.084
170523	1360393	133	0.004	0.133
170524	1360394	48	0.001	0.048
170525	1360395	21	<0.001	0.021
170526	1360396	32	<0.001	0.032
170527	1360397	19	<0.001	0.019
170528	1360398	25	<0.001	0.025
170529	1360399	31	<0.001	0.031
170530	1360400	1724	0.050	1.724
170531	1360401	19	<0.001	0.019
170532 Dup	1360401	17	<0.001	0.017
170533	1360402	15	<0.001	0.015
170534	1360403	34	<0.001	0.034
170535	1360404	17	<0.001	0.017
170536	1360405	23	<0.001	0.023
170537	1360406	45	0.001	0.045
170538	1360407	13	<0.001	0.013
170539	1360408	14	<0.001	0.014
170540	1360409	12	<0.001	0.012
170541	1360410	<5	<0.001	<0.005
170542	1360411	10	<0.001	0.010

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, June 27, 2012

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/15/2012
 Date Completed: 06/27/2012
 Job #: 201242109
 Reference: TK 12 248
 Sample #: 252

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
170543 Dup	1360411	10	<0.001	0.010
170544	1360412	19	<0.001	0.019
170545	1360413	6	<0.001	0.006
170546	1360414	<5	<0.001	<0.005
170547	1360415	14	<0.001	0.014
170548	1360416	6	<0.001	0.006
170549	1360417	23	<0.001	0.023
170550	1360418	9	<0.001	0.009
170551	1360419	26	<0.001	0.026
170552	1360420	4920	0.144	4.920
170553	1360421	17	<0.001	0.017
170554 Rep	1360421	16	<0.001	0.016
170555	1360422	44	0.001	0.044
170556	1360423	36	0.001	0.036
170557	1360424	41	0.001	0.041
170558	1360425	24	<0.001	0.024
170559	1360426	36	0.001	0.036
170560	1360427	48	0.001	0.048
170561	1360428	65	0.002	0.065
170562	1360429	88	0.003	0.088
170563	1360430	6	<0.001	0.006
170564	1360431	6	<0.001	0.006
170565 Dup	1360431	<5	<0.001	<0.005
170566	1360432	<5	<0.001	<0.005
170567	1360433	19	<0.001	0.019
170568	1360434	9	<0.001	0.009
170569	1360435	11	<0.001	0.011
170570	1360436	12	<0.001	0.012
170571	1360437	30	<0.001	0.030
170572	1360438	21	<0.001	0.021

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, June 27, 2012

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/15/2012
 Date Completed: 06/27/2012
 Job #: 201242109
 Reference: TK 12 248
 Sample #: 252

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
170573	1360439	11	<0.001	0.011
170574	1360440	240	0.007	0.240
170575	1360441	129	0.004	0.129
170576 Dup	1360441	190	0.006	0.190
170577	1360442	2174	0.063	2.174
170578	1360443	51	0.001	0.051
170579	1360444	217	0.006	0.217
170580	1360445	<5	<0.001	<0.005
170581	1360446	19	<0.001	0.019
170582	1360447	105	0.003	0.105
170583	1360448	128	0.004	0.128
170584	1360449	1454	0.042	1.454
170585	1360450	<5	<0.001	<0.005
170586	1360451	84	0.002	0.084
170587 Dup	1360451	69	0.002	0.069
170588	1360452	258	0.008	0.258
170589	1360453	284	0.008	0.284
170590	1360454	126	0.004	0.126
170591	1360455	372	0.011	0.372
170592	1360456	502	0.015	0.502
170593	1360457	20	<0.001	0.020
170594	1360458	126	0.004	0.126
170595	1360459	185	0.005	0.185
170596	1360460	1791	0.052	1.791
170597	1360461	27	<0.001	0.027
170598 Dup	1360461	17	<0.001	0.017
170599	1360462	229	0.007	0.229
170600	1360463	111	0.003	0.111
170601	1360464	12438	0.363	12.438
170602	1360465	89	0.003	0.089

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, June 27, 2012

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/15/2012
 Date Completed: 06/27/2012
 Job #: 201242109
 Reference: TK 12 248
 Sample #: 252

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
170603	1360466	83	0.002	0.083
170604	1360467	254	0.007	0.254
170605	1360468	498	0.015	0.498
170606	1360469	43	0.001	0.043
170607	1360470	<5	<0.001	<0.005
170608	1360471	423	0.012	0.423
170609 Dup	1360471	356	0.010	0.356
170610	1360472	479	0.014	0.479
170611	1360473	298	0.009	0.298
170612	1360474	15	<0.001	0.015
170613	1360475	93	0.003	0.093
170614	1360476	100	0.003	0.100
170615	1360477	139	0.004	0.139
170616	1360478	247	0.007	0.247
170617	1360479	81	0.002	0.081
170618	1360480	4869	0.142	4.869
170619	1360481	17	<0.001	0.017
170620 Rep	1360481	12	<0.001	0.012
170621	1360482	28	<0.001	0.028
170622	1360483	17	<0.001	0.017
170623	1360484	30	<0.001	0.030
170624	1360485	20	<0.001	0.020
170625	1360486	19	<0.001	0.019
170626	1360487	21	<0.001	0.021
170627	1360488	30	<0.001	0.030
170628	1360489	20	<0.001	0.020
170629	1360490	12	<0.001	0.012
170630	1360491	15	<0.001	0.015
170631 Dup	1360491	15	<0.001	0.015
170632	1360492	11	<0.001	0.011

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.

The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, June 27, 2012

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/15/2012
 Date Completed: 06/27/2012
 Job #: 201242109
 Reference: TK 12 248
 Sample #: 252

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
170633	1360493	46	0.001	0.046
170634	1360494	19	<0.001	0.019
170635	1360495	17	<0.001	0.017
170636	1360496	17	<0.001	0.017
170637	1360497	9	<0.001	0.009
170638	1360498	<5	<0.001	<0.005
170639	1360499	<5	<0.001	<0.005
170640	1360500	230	0.007	0.230
170641	1360501	6	<0.001	0.006
170642 Dup	1360501	5	<0.001	0.005
170643	1360502	7	<0.001	0.007
170644	1360503	<5	<0.001	<0.005
170645	1360504	7	<0.001	0.007
170646	1360505	<5	<0.001	<0.005
170647	1360506	5	<0.001	0.005
170648	1360507	9	<0.001	0.009
170649	1360508	16	<0.001	0.016
170650	1360509	20	<0.001	0.020
170651	1360510	6	<0.001	0.006
170652	1360511	35	0.001	0.035
170653 Dup	1360511	35	0.001	0.035
170654	1360512	53	0.002	0.053
170655	1360513	33	<0.001	0.033
170656	1360514	10	<0.001	0.010
170657	1360515	12	<0.001	0.012
170658	1360516	12	<0.001	0.012
170659	1360517	37	0.001	0.037
170660	1360518	55	0.002	0.055
170661	1360519	24	<0.001	0.024
170662	1360520	1864	0.054	1.864

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.

The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, June 27, 2012

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/15/2012
 Date Completed: 06/27/2012
 Job #: 201242109
 Reference: TK 12 248
 Sample #: 252

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
170663	1360521	101	0.003	0.101
170664 Dup	1360521	124	0.004	0.124
170665	1360522	21	<0.001	0.021
170666	1360523	47	0.001	0.047
170667	1360524	24	<0.001	0.024
170668	1360525	17	<0.001	0.017
170669	1360526	15	<0.001	0.015
170670	1360527	8	<0.001	0.008
170671	1360528	9	<0.001	0.009
170672	1360529	9	<0.001	0.009
170673	1360530	<5	<0.001	<0.005
170674	1360531	95	0.003	0.095
170675 Dup	1360531	100	0.003	0.100
170676	1360532	189	0.006	0.189
170677	1360533	36	0.001	0.036
170678	1360534	5	<0.001	0.005
170679	1360535	14	<0.001	0.014
170680	1360536	<5	<0.001	<0.005
170681	1360537	<5	<0.001	<0.005
170682	1360538	7	<0.001	0.007
170683	1360539	<5	<0.001	<0.005
170684	1360540	4977	0.145	4.977
170685	1360541	8	<0.001	0.008
170686 Rep	1360541	6	<0.001	0.006
170687	1360542	9	<0.001	0.009
170688	1360543	23	<0.001	0.023
170689	1360544	8	<0.001	0.008
170690	1360545	<5	<0.001	<0.005
170691	1360546	9	<0.001	0.009
170692	1360547	6	<0.001	0.006

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.

The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, June 27, 2012

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/15/2012
 Date Completed: 06/27/2012
 Job #: 201242109
 Reference: TK 12 248
 Sample #: 252

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
170693	1360548	21	<0.001	0.021
170694	1360549	10	<0.001	0.010
170695	1360550	<5	<0.001	<0.005
170696	1360551	<5	<0.001	<0.005
170697 Dup	1360551	6	<0.001	0.006
170698	1360552	9	<0.001	0.009
170699	1360553	5	<0.001	0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AlSu1

 Certified By: 
 Derek Demianliuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.

The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, July 13, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/28/2012
 Date Completed: 07/13/2012
 Job #: 201242391
 Reference: TL 12 249
 Sample #: 234

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
182154	1305459	87	0.003	0.087
182155	1305460	<5	<0.001	<0.005
182156	1305461	214	0.006	0.214
182157	1305462	20	<0.001	0.020
182158	1305463	7	<0.001	0.007
182159	1305464	7	<0.001	0.007
182160	1305465	177	0.005	0.177
182161	1305466	<5	<0.001	<0.005
182162	1305467	<5	<0.001	<0.005
182163	1305468	7	<0.001	0.007
182164 Dup	1305468	<5	<0.001	<0.005
182165	1305469	<5	<0.001	<0.005
182166	1305470	2002	0.058	2.002
182167	1305471	<5	<0.001	<0.005
182168	1305472	<5	<0.001	<0.005
182169	1305473	30	<0.001	0.030
182170	1305474	7	<0.001	0.007
182171	1305475	49	0.001	0.049
182172	1305476	16	<0.001	0.016
182173	1305477	<5	<0.001	<0.005
182174	1305478	<5	<0.001	<0.005
182175 Dup	1305478	19	<0.001	0.019
182176	1305479	6	<0.001	0.006
182177	1305480	<5	<0.001	<0.005
182178	1305481	26	<0.001	0.026
182179	1305482	3321	0.097	3.321
182180	1305483	20	<0.001	0.020
182181	1305484	206	0.006	0.206
182182	1305485	10	<0.001	0.010
182183	1305486	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, July 13, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/28/2012
 Date Completed: 07/13/2012
 Job #: 201242391
 Reference: TL 12 249
 Sample #: 234

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
182184	1305487	<5	<0.001	<0.005
182185	1305488	<5	<0.001	<0.005
182186 Dup	1305488	28	<0.001	0.028
182187	1305489	86	0.003	0.086
182188	1305490	241	0.007	0.241
182189	1305491	118	0.003	0.118
182190	1305492	21	<0.001	0.021
182191	1305493	9	<0.001	0.009
182192	1305494	14	<0.001	0.014
182193	1305495	17	<0.001	0.017
182194	1305496	20	<0.001	0.020
182195	1305497	6	<0.001	0.006
182196	1305498	<5	<0.001	<0.005
182197 Dup	1305498	6	<0.001	0.006
182198	1305499	6	<0.001	0.006
182199	1305500	<5	<0.001	<0.005
182200	1305501	20	<0.001	0.020
182201	1305502	166	0.005	0.166
182202	1305503	133	0.004	0.133
182203	1305504	45	0.001	0.045
182204	1305505	107	0.003	0.107
182205	1305506	45	0.001	0.045
182206	1305507	21	<0.001	0.021
182207	1305508	31	<0.001	0.031
182208 Dup	1305508	40	0.001	0.040
182209	1305509	55	0.002	0.055
182210	1305510	1969	0.057	1.969
182211	1305511	32	<0.001	0.032
182212	1305512	27	<0.001	0.027
182213	1305513	25	<0.001	0.025

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, July 13, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/28/2012
 Date Completed: 07/13/2012
 Job #: 201242391
 Reference: TL 12 249
 Sample #: 234

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
182214	1305514	52	0.002	0.052
182215	1305515	40	0.001	0.040
182216	1305516	39	0.001	0.039
182217	1305517	240	0.007	0.240
182218	1305518	24	<0.001	0.024
182219 Rep	1305518	28	<0.001	0.028
182220	1305519	11	<0.001	0.011
182221	1305520	<5	<0.001	<0.005
182222	1305521	7	<0.001	0.007
182223	1305522	21	<0.001	0.021
182224	1305523	159	0.005	0.159
182225	1305524	96	0.003	0.096
182226	1305525	19	<0.001	0.019
182227	1305526	19	<0.001	0.019
182228	1305527	<5	<0.001	<0.005
182229	1305528	87	0.003	0.087
182230 Dup	1305528	74	0.002	0.074
182231	1305529	45	0.001	0.045
182232	1305530	248	0.007	0.248
182233	1305531	19	<0.001	0.019
182234	1305532	15	<0.001	0.015
182235	1305533	13	<0.001	0.013
182236	1305534	18	<0.001	0.018
182237	1305535	897	0.026	0.897
182238	1305536	748	0.022	0.748
182239	1305537	32	<0.001	0.032
182240	1305538	49	0.001	0.049
182241 Dup	1305538	120	0.003	0.120
182242	1305539	61	0.002	0.061
182243	1305540	7	<0.001	0.007

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, July 13, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/28/2012
 Date Completed: 07/13/2012
 Job #: 201242391
 Reference: TL 12 249
 Sample #: 234

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
182244	1305541	695	0.020	0.695
182245	1305542	331	0.010	0.331
182246	1305543	87	0.003	0.087
182247	1305544	52	0.002	0.052
182248	1305545	16	<0.001	0.016
182249	1305546	38	0.001	0.038
182250	1305547	54	0.002	0.054
182251	1305548	237	0.007	0.237
182252 Dup	1305548	167	0.005	0.167
182253	1305549	12	<0.001	0.012
182254	1305550	5156	0.150	5.156
182255	1305551	18	<0.001	0.018
182256	1305552	16	<0.001	0.016
182257	1305553	14	<0.001	0.014
182258	1305554	147	0.004	0.147
182259	1305555	73	0.002	0.073
182260	1305556	72	0.002	0.072
182261	1305557	90	0.003	0.090
182262	1305558	249	0.007	0.249
182263 Dup	1305558	14	<0.001	0.014
182264	1305559	47	0.001	0.047
182265	1305560	<5	<0.001	<0.005
182266	1305561	29	<0.001	0.029
182267	1305562	135	0.004	0.135
182268	1305563	38	0.001	0.038
182269	1305564	6	<0.001	0.006
182270	1305565	16	<0.001	0.016
182271	1305566	91	0.003	0.091
182272	1305567	15	<0.001	0.015
182273	1305568	48	0.001	0.048

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, July 13, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/28/2012
 Date Completed: 07/13/2012
 Job #: 201242391
 Reference: TL 12 249
 Sample #: 234

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
182274 Dup	1305568	55	0.002	0.055
182275	1305569	21	<0.001	0.021
182276	1305570	1919	0.056	1.919
182277	1305571	19	<0.001	0.019
182278	1305572	9	<0.001	0.009
182279	1305573	31	<0.001	0.031
182280	1305574	37	0.001	0.037
182281	1305575	15	<0.001	0.015
182282	1305576	11	<0.001	0.011
182283	1305577	27	<0.001	0.027
182284	1305578	24	<0.001	0.024
182285 Rep	1305578	19	<0.001	0.019
182286	1305579	43	0.001	0.043
182287	1305580	12	<0.001	0.012
182288	1305581	17	<0.001	0.017
182289	1305582	23	<0.001	0.023
182290	1305583	16	<0.001	0.016
182291	1305584	21	<0.001	0.021
182292	1305585	11	<0.001	0.011
182293	1305586	9	<0.001	0.009
182294	1305587	<5	<0.001	<0.005
182295	1305588	10	<0.001	0.010
182296 Dup	1305588	15	<0.001	0.015
182297	1305589	20	<0.001	0.020
182298	1305590	244	0.007	0.244
182299	1305591	30	<0.001	0.030
182300	1305592	419	0.012	0.419
182301	1305593	39	0.001	0.039
182302	1305594	68	0.002	0.068
182303	1305595	26	<0.001	0.026

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, July 13, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/28/2012
 Date Completed: 07/13/2012
 Job #: 201242391
 Reference: TL 12 249
 Sample #: 234

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
182304	1305596	43	0.001	0.043
182305	1305597	<5	<0.001	<0.005
182306	1305598	13	<0.001	0.013
182307 Dup	1305598	16	<0.001	0.016
182308	1305599	116	0.003	0.116
182309	1305600	<5	<0.001	<0.005
182310	1305601	61	0.002	0.061
182311	1305602	58	0.002	0.058
182312	1305603	20	<0.001	0.020
182313	1305604	<5	<0.001	<0.005
182314	1305605	11	<0.001	0.011
182315	1305606	167	0.005	0.167
182316	1305607	9	<0.001	0.009
182317	1305608	5	<0.001	0.005
182318 Dup	1305608	43	0.001	0.043
182319	1305609	20	<0.001	0.020
182320	1305610	5565	0.162	5.565
182321	1305611	<5	<0.001	<0.005
182322	1305612	20	<0.001	0.020
182323	1305613	<5	<0.001	<0.005
182324	1305614	<5	<0.001	<0.005
182325	1305615	<5	<0.001	<0.005
182326	1305616	<5	<0.001	<0.005
182327	1305617	8	<0.001	0.008
182328	1305618	90	0.003	0.090
182329 Dup	1305618	64	0.002	0.064
182330	1305619	195	0.006	0.195
182331	1305620	7	<0.001	0.007
182332	1305621	23	<0.001	0.023
182333	1305622	27	<0.001	0.027

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, July 13, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/28/2012
 Date Completed: 07/13/2012
 Job #: 201242391
 Reference: TL 12 249
 Sample #: 234

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
182334	1305623	15	<0.001	0.015
182335	1305624	7	<0.001	0.007
182336	1305625	15	<0.001	0.015
182337	1305626	5	<0.001	0.005
182338	1305627	<5	<0.001	<0.005
182339	1305628	<5	<0.001	<0.005
182340 Dup	1305628	<5	<0.001	<0.005
182341	1305629	6	<0.001	0.006
182342	1305630	2053	0.060	2.053
182343	1305631	8	<0.001	0.008
182344	1305632	11	<0.001	0.011
182345	1305633	27	<0.001	0.027
182346	1305634	49	0.001	0.049
182347	1305635	89	0.003	0.089
182348	1305636	292	0.009	0.292
182349	1305637	26	<0.001	0.026
182350	1305638	60	0.002	0.060
182351 Rep	1305638	37	0.001	0.037
182352	1305639	<5	<0.001	<0.005
182353	1305640	<5	<0.001	<0.005
182354	1305641	6	<0.001	0.006
182355	1305642	<5	<0.001	<0.005
182356	1305643	12	<0.001	0.012
182357	1305644	14	<0.001	0.014
182358	1305645	6	<0.001	0.006
182359	1305646	31	<0.001	0.031
182360	1305647	15	<0.001	0.015
182361	1305648	24	<0.001	0.024
182362 Dup	1305648	9	<0.001	0.009
182363	1305649	59	0.002	0.059

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, July 13, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/28/2012
 Date Completed: 07/13/2012
 Job #: 201242391
 Reference: TL 12 249
 Sample #: 234

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
182364	1305650	240	0.007	0.240
182365	1305651	11	<0.001	0.011
182366	1305652	10	<0.001	0.010
182367	1305653	58	0.002	0.058
182368	1305654	13	<0.001	0.013
182369	1305655	36	0.001	0.036
182370	1305656	34	0.001	0.034
182371	1305657	12	<0.001	0.012
182372	1305658	12	<0.001	0.012
182373 Dup	1305658	83	0.002	0.083
182374	1305659	32	<0.001	0.032
182375	1305660	<5	<0.001	<0.005
182376	1305661	50	0.001	0.050
182377	1305662	16	<0.001	0.016
182378	1305663	17	<0.001	0.017
182379	1305664	138	0.004	0.138
182380	1305665	23	<0.001	0.023
182381	1305666	9	<0.001	0.009
182382	1305667	56	0.002	0.056
182383	1305668	37	0.001	0.037
182384 Dup	1305668	31	<0.001	0.031
182385	1305669	38	0.001	0.038
182386	1305670	4855	0.142	4.855
182387	1305671	11	<0.001	0.011
182388	1305672	5	<0.001	0.005
182389	1305673	27	<0.001	0.027
182390	1305674	24	<0.001	0.024
182391	1305675	<5	<0.001	<0.005
182392	1305676	<5	<0.001	<0.005
182393	1305677	9	<0.001	0.009

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, July 13, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/28/2012
 Date Completed: 07/13/2012
 Job #: 201242391
 Reference: TL 12 249
 Sample #: 234

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
182394	1305678	35	0.001	0.035
182395 Dup	1305678	35	0.001	0.035
182396	1305679	36	0.001	0.036
182397	1305680	8	<0.001	0.008
182398	1305681	100	0.003	0.100
182399	1305682	22	<0.001	0.022
182400	1305683	39	0.001	0.039
182401	1305684	25	<0.001	0.025
182402	1305685	17	<0.001	0.017
182403	1305686	8	<0.001	0.008
182404	1305687	27	<0.001	0.027
182405	1305688	79	0.002	0.079
182406 Dup	1305688	79	0.002	0.079
182407	1305689	20	<0.001	0.020
182408	1305690	1530	0.045	1.530
182409	1305691	9	<0.001	0.009
182410	1305692	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Tuesday, July 10, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/22/2012
 Date Completed: 07/10/2012
 Job #: 201242304
 Reference: TL 12 250
 Sample #: 201

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
177815	1305693	6	<0.001	0.006
177816	1305694	42	0.001	0.042
177817	1305695	26	<0.001	0.026
177818	1305696	24	<0.001	0.024
177819	1305697	7	<0.001	0.007
177820	1305698	31	<0.001	0.031
177821	1305699	16	<0.001	0.016
177822	1305700	<5	<0.001	<0.005
177823	1305701	7	<0.001	0.007
177824	1305702	5	<0.001	0.005
177825 Dup	1305702	<5	<0.001	<0.005
177826	1305703	<5	<0.001	<0.005
177827	1305704	<5	<0.001	<0.005
177828	1305705	<5	<0.001	<0.005
177829	1305706	<5	<0.001	<0.005
177830	1305707	<5	<0.001	<0.005
177831	1305708	<5	<0.001	<0.005
177832	1305709	<5	<0.001	<0.005
177833	1305710	<5	<0.001	<0.005
177834	1305711	<5	<0.001	<0.005
177835	1305712	<5	<0.001	<0.005
177836 Dup	1305712	<5	<0.001	<0.005
177837	1305713	<5	<0.001	<0.005
177838	1305714	<5	<0.001	<0.005
177839	1305715	<5	<0.001	<0.005
177840	1305716	<5	<0.001	<0.005
177841	1305717	6	<0.001	0.006
177842	1305718	<5	<0.001	<0.005
177843	1305719	<5	<0.001	<0.005
177844	1305720	222	0.006	0.222

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Tuesday, July 10, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/22/2012
 Date Completed: 07/10/2012
 Job #: 201242304
 Reference: TL 12 250
 Sample #: 201

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
177845	1305721	<5	<0.001	<0.005
177846	1305722	<5	<0.001	<0.005
177847 Dup	1305722	<5	<0.001	<0.005
177848	1305723	7	<0.001	0.007
177849	1305724	<5	<0.001	<0.005
177850	1305725	<5	<0.001	<0.005
177851	1305726	<5	<0.001	<0.005
177852	1305727	6	<0.001	0.006
177853	1305728	<5	<0.001	<0.005
177854	1305729	6	<0.001	0.006
177855	1305730	14	<0.001	0.014
177856	1305731	<5	<0.001	<0.005
177857	1305732	<5	<0.001	<0.005
177858 Dup	1305732	<5	<0.001	<0.005
177859	1305733	<5	<0.001	<0.005
177860	1305734	5	<0.001	0.005
177861	1305735	<5	<0.001	<0.005
177862	1305736	11	<0.001	0.011
177863	1305737	<5	<0.001	<0.005
177864	1305738	14	<0.001	0.014
177865	1305739	<5	<0.001	<0.005
177866	1305740	<5	<0.001	<0.005
177867	1305741	<5	<0.001	<0.005
177868	1305742	6	<0.001	0.006
177869 Dup	1305742	<5	<0.001	<0.005
177870	1305743	<5	<0.001	<0.005
177871	1305744	5	<0.001	0.005
177872	1305745	6	<0.001	0.006
177873	1305746	8	<0.001	0.008
177874	1305747	7	<0.001	0.007

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Tuesday, July 10, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/22/2012
 Date Completed: 07/10/2012
 Job #: 201242304
 Reference: TL 12 250
 Sample #: 201

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
177875	1305748	5	<0.001	0.005
177876	1305749	6	<0.001	0.006
177877	1305750	6	<0.001	0.006
177878	1305751	<5	<0.001	<0.005
177879	1305752	<5	<0.001	<0.005
177880 Rep	1305752	<5	<0.001	<0.005
177881	1305753	8	<0.001	0.008
177882	1305754	<5	<0.001	<0.005
177883	1305755	6	<0.001	0.006
177884	1305756	7	<0.001	0.007
177885	1305757	<5	<0.001	<0.005
177886	1305758	70	0.002	0.070
177887	1305759	5862	0.171	5.862
177888	1305760	5154	0.150	5.154
177889	1305761	63	0.002	0.063
177890	1305762	<5	<0.001	<0.005
177891 Dup	1305762	57	0.002	0.057
177892	1305763	<5	<0.001	<0.005
177893	1305764	<5	<0.001	<0.005
177894	1305765	<5	<0.001	<0.005
177895	1305766	<5	<0.001	<0.005
177896	1305767	<5	<0.001	<0.005
177897	1305768	<5	<0.001	<0.005
177898	1305769	<5	<0.001	<0.005
177899	1305770	<5	<0.001	<0.005
177900	1305771	<5	<0.001	<0.005
177901	1305772	<5	<0.001	<0.005
177902 Dup	1305772	<5	<0.001	<0.005
177903	1305773	<5	<0.001	<0.005
177904	1305774	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Tuesday, July 10, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/22/2012
 Date Completed: 07/10/2012
 Job #: 201242304
 Reference: TL 12 250
 Sample #: 201

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
177905	1305775	<5	<0.001	<0.005
177906	1305776	5	<0.001	0.005
177907	1305777	30	<0.001	0.030
177908	1305778	13	<0.001	0.013
177909	1305779	5	<0.001	0.005
177910	1305780	6	<0.001	0.006
177911	1305781	23	<0.001	0.023
177912	1305782	94	0.003	0.094
177913 Dup	1305782	84	0.002	0.084
177914	1305783	11	<0.001	0.011
177915	1305784	<5	<0.001	<0.005
177916	1305785	30	<0.001	0.030
177917	1305786	22	<0.001	0.022
177918	1305787	12	<0.001	0.012
177919	1305788	5	<0.001	0.005
177920	1305789	<5	<0.001	<0.005
177921	1305790	<5	<0.001	<0.005
177922	1305791	<5	<0.001	<0.005
177923	1305792	<5	<0.001	<0.005
177924 Dup	1305792	<5	<0.001	<0.005
177925	1305793	<5	<0.001	<0.005
177926	1305794	<5	<0.001	<0.005
177927	1305795	<5	<0.001	<0.005
177928	1305796	<5	<0.001	<0.005
177929	1305797	<5	<0.001	<0.005
177930	1305798	<5	<0.001	<0.005
177931	1305799	<5	<0.001	<0.005
177932	1305800	2062	0.060	2.062
177933	1305801	<5	<0.001	<0.005
177934	1305802	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Tuesday, July 10, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/22/2012
 Date Completed: 07/10/2012
 Job #: 201242304
 Reference: TL 12 250
 Sample #: 201

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
177935 Dup	1305802	<5	<0.001	<0.005
177936	1305803	<5	<0.001	<0.005
177937	1305804	<5	<0.001	<0.005
177938	1305805	<5	<0.001	<0.005
177939	1305806	<5	<0.001	<0.005
177940	1305807	5	<0.001	0.005
177941	1305808	<5	<0.001	<0.005
177942	1305809	<5	<0.001	<0.005
177943	1305810	<5	<0.001	<0.005
177944	1305811	<5	<0.001	<0.005
177945	1305812	<5	<0.001	<0.005
177946 Rep	1305812	6	<0.001	0.006
177947	1305813	<5	<0.001	<0.005
177948	1305814	<5	<0.001	<0.005
177949	1305815	<5	<0.001	<0.005
177950	1305816	<5	<0.001	<0.005
177951	1305817	<5	<0.001	<0.005
177952	1305818	48	0.001	0.048
177953	1305819	<5	<0.001	<0.005
177954	1305820	<5	<0.001	<0.005
177955	1305821	<5	<0.001	<0.005
177956	1305822	<5	<0.001	<0.005
177957 Dup	1305822	<5	<0.001	<0.005
177958	1305823	<5	<0.001	<0.005
177959	1305824	<5	<0.001	<0.005
177960	1305825	6	<0.001	0.006
177961	1305826	6	<0.001	0.006
177962	1305827	<5	<0.001	<0.005
177963	1305828	<5	<0.001	<0.005
177964	1305829	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Tuesday, July 10, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/22/2012
 Date Completed: 07/10/2012
 Job #: 201242304
 Reference: TL 12 250
 Sample #: 201

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
177965	1305830	<5	<0.001	<0.005
177966	1305831	<5	<0.001	<0.005
177967	1305832	<5	<0.001	<0.005
177968 Dup	1305832	<5	<0.001	<0.005
177969	1305833	<5	<0.001	<0.005
177970	1305834	<5	<0.001	<0.005
177971	1305835	<5	<0.001	<0.005
177972	1305836	<5	<0.001	<0.005
177973	1305837	<5	<0.001	<0.005
177974	1305838	<5	<0.001	<0.005
177975	1305839	7	<0.001	0.007
177976	1305840	261	0.008	0.261
177977	1305841	<5	<0.001	<0.005
177978	1305842	<5	<0.001	<0.005
177979 Dup	1305842	<5	<0.001	<0.005
177980	1305843	<5	<0.001	<0.005
177981	1305844	<5	<0.001	<0.005
177982	1305845	<5	<0.001	<0.005
177983	1305846	<5	<0.001	<0.005
177984	1305847	<5	<0.001	<0.005
177985	1305848	<5	<0.001	<0.005
177986	1305849	<5	<0.001	<0.005
177987	1305850	<5	<0.001	<0.005
177988	1305851	<5	<0.001	<0.005
177989	1305852	<5	<0.001	<0.005
177990 Dup	1305852	10	<0.001	0.010
177991	1305853	13	<0.001	0.013
177992	1305854	<5	<0.001	<0.005
177993	1305855	<5	<0.001	<0.005
177994	1305856	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Tuesday, July 10, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/22/2012
 Date Completed: 07/10/2012
 Job #: 201242304
 Reference: TL 12 250
 Sample #: 201

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
177995	1305857	<5	<0.001	<0.005
177996	1305858	<5	<0.001	<0.005
177997	1305859	<5	<0.001	<0.005
177998	1305860	<5	<0.001	<0.005
177999	1305861	<5	<0.001	<0.005
178000	1305862	<5	<0.001	<0.005
178001 Dup	1305862	<5	<0.001	<0.005
178002	1305863	<5	<0.001	<0.005
178003	1305864	<5	<0.001	<0.005
178004	1305865	<5	<0.001	<0.005
178005	1305866	<5	<0.001	<0.005
178006	1305867	<5	<0.001	<0.005
178007	1305868	<5	<0.001	<0.005
178008	1305869	<5	<0.001	<0.005
178009	1305870	<5	<0.001	<0.005
178010	1305871	<5	<0.001	<0.005
178011	1305872	<5	<0.001	<0.005
178012 Rep	1305872	<5	<0.001	<0.005
178013	1305873	<5	<0.001	<0.005
178014	1305874	<5	<0.001	<0.005
178015	1305875	<5	<0.001	<0.005
178016	1305876	<5	<0.001	<0.005
178017	1305877	<5	<0.001	<0.005
178018	1305878	<5	<0.001	<0.005
178019	1305879	<5	<0.001	<0.005
178020	1305880	4982	0.145	4.982
178021	1305881	6	<0.001	0.006
178022	1305882	<5	<0.001	<0.005
178023 Dup	1305882	<5	<0.001	<0.005
178024	1305883	5	<0.001	0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Tuesday, July 10, 2012


Preliminary Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 06/22/2012
 Date Completed: 07/10/2012
 Job #: 201242304
 Reference: TL 12 250
 Sample #: 201

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
178025	1305884	<5	<0.001	<0.005
178026	1305885	<5	<0.001	<0.005
178027	1305886	<5	<0.001	<0.005
178028	1305887	<5	<0.001	<0.005
178029	1305888	<5	<0.001	<0.005
178030	1305889	<5	<0.001	<0.005
178031	1305890	<5	<0.001	<0.005
178032	1305891	<5	<0.001	<0.005
178033	1305892	<5	<0.001	<0.005
178034 Dup	1305892	<5	<0.001	<0.005
178035	1305893	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/04/2012
 Date Completed:
 Job #: 201242633
 Reference: TL 12 251
 Sample #: 222

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
196579	1305894	0.008	<1	2.63	3	299	<2	8	1.13	<4	4	14	4	1.56	<0.01	7	0.56	165	<1	27	395	8	0.44	<5	<5	<10	358	565	<2	29	<10	6	33
196580	1305895	0.006	<1	3.23	2	414	<2	4	1.54	<4	5	28	4	1.61	<0.01	7	0.58	226	<1	50	408	7	0.42	<5	<5	<10	467	1093	<2	31	<10	5	37
196581	1305896	<0.005	<1	4.06	5	593	<2	<1	1.77	<4	15	71	41	2.67	<0.01	14	0.89	333	2	86	473	9	0.69	<5	<5	<10	398	1785	3	51	<10	8	49
196582	1305897	<0.005	<1	4.17	6	691	<2	<1	1.51	<4	6	27	12	1.57	<0.01	6	0.61	201	<1	51	357	7	0.46	<5	<5	<10	346	1178	<2	30	<10	5	37
196583	1305898	<0.005	<1	3.04	<2	585	<2	<1	1.53	<4	5	25	7	1.31	<0.01	2	0.46	182	<1	42	330	10	0.35	<5	<5	<10	285	1265	<2	25	<10	4	41
196584	1305899	<0.005	1	4.32	<2	684	2	6	2.39	<4	20	144	39	3.44	<0.01	16	1.24	508	1	100	531	16	1.11	<5	<5	<10	359	2582	2	83	<10	13	52
196585	1305900	<0.005	<1	6.01	4	468	<2	<1	3.20	4	21	68	31	4.34	0.13	15	1.75	825	<1	46	772	6	0.51	5	<5	<10	374	3432	9	143	24	21	67
196586	1305901	<0.005	1	3.67	<2	502	2	2	1.74	<4	21	154	36	3.83	<0.01	16	1.39	488	<1	97	554	19	0.99	<5	<5	<10	346	2406	<2	87	<10	13	66
196587	1305902	<0.005	1	4.57	6	492	2	7	1.42	5	28	157	52	5.15	<0.01	28	1.81	617	<1	113	540	16	1.50	6	<5	<10	342	2646	4	108	<10	12	96
196588	1305903	0.011	<1	3.37	3	454	<2	4	1.47	<4	18	150	54	3.78	<0.01	13	1.34	556	<1	104	518	16	1.16	<5	<5	<10	310	2126	<2	78	<10	12	61
196589D	1305903	<0.005	<1	3.29	<2	441	<2	<1	1.44	<4	20	149	54	3.77	<0.01	14	1.33	541	<1	101	510	16	1.19	<5	<5	<10	299	2040	2	77	<10	11	63
196590	1305904	0.011	2	3.78	8	483	2	8	1.25	4	25	158	58	4.44	<0.01	23	1.50	475	2	115	599	19	1.24	<5	<5	<10	266	2769	<2	100	<10	11	83
196591	1305905	0.011	1	4.60	4	380	2	5	2.23	4	24	150	54	4.64	0.09	20	2.02	641	<1	96	594	27	0.70	<5	<5	<10	265	2852	<2	109	<10	14	81
196592	1305906	0.032	<1	4.48	4	405	2	1	2.28	4	25	152	52	4.78	0.08	18	2.03	706	<1	95	602	15	0.64	<5	<5	<10	313	3237	<2	112	<10	13	84
196593	1305907	<0.005	<1	4.56	12	313	2	<1	1.38	4	24	147	45	4.16	<0.01	21	1.59	605	<1	89	589	18	0.62	<5	<5	<10	249	3082	<2	96	<10	13	76
196594	1305908	0.007	<1	5.01	12	435	2	5	1.84	<4	24	156	55	3.82	<0.01	23	1.35	638	<1	86	637	33	0.61	<5	<5	<10	400	3407	5	103	<10	14	71
196595	1305909	<0.005	<1	5.07	28	348	2	2	1.38	4	25	161	44	4.65	<0.01	25	1.68	660	<1	96	595	22	0.50	5	<5	<10	281	3526	2	117	<10	14	74
196596	1305910	0.007	1	5.27	16	348	<2	8	1.83	<4	22	151	53	3.80	<0.01	26	1.44	507	<1	91	585	15	0.71	<5	<5	<10	339	2967	<2	84	<10	16	44
196597	1305911	0.009	1	5.38	25	394	2	<1	1.75	4	25	148	52	4.44	0.20	20	1.53	511	<1	93	560	20	0.84	<5	<5	<10	306	3244	<2	107	<10	15	79
196598	1305912	0.134	1	3.57	<2	325	2	<1	1.49	<4	17	108	44	2.90	<0.01	13	1.13	441	<1	78	383	24	0.98	<5	<5	<10	308	2105	2	79	<10	13	39

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/04/2012
 Date Completed:
 Job #: 201242633
 Reference: TL 12 251
 Sample #: 222

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
196599	1305913	<0.005	1	4.41	20	420	2	9	1.86	4	25	154	47	4.16	<0.01	18	1.28	661	<1	92	561	15	0.73	<5	<5	<10	285	3020	<2	97	<10	12	71
196600D	1305913	<0.005	1	3.92	19	417	2	10	1.86	<4	25	154	46	4.12	<0.01	18	1.25	658	<1	88	561	17	0.71	<5	<5	<10	287	3097	<2	98	<10	12	72
196601	1305914	0.012	1	4.10	4	394	2	4	2.43	<4	23	167	47	4.13	<0.01	17	1.26	746	<1	100	484	23	1.14	<5	<5	<10	343	2862	<2	95	<10	12	63
196602	1305915	0.024	1	4.22	3	355	2	<1	2.28	4	23	161	60	4.72	<0.01	24	1.63	735	<1	98	668	20	1.20	<5	<5	<10	305	2441	4	101	<10	14	73
196603	1305916	0.013	1	4.53	<2	376	<2	3	1.43	4	22	140	54	4.25	<0.01	20	1.55	538	<1	81	523	19	1.10	<5	<5	<10	254	2396	3	91	<10	14	67
196604	1305917	0.006	<1	5.30	28	493	<2	6	0.74	4	27	153	54	4.62	<0.01	24	1.60	379	<1	96	571	15	0.64	6	<5	<10	175	3097	4	116	<10	14	99
196605	1305918	0.005	<1	5.25	29	300	2	3	1.31	4	25	147	41	4.62	<0.01	27	1.71	520	<1	90	567	17	0.57	<5	<5	<10	237	2850	<2	99	<10	15	82
196606	1305919	<0.005	<1	4.65	21	404	2	2	1.75	<4	23	152	43	3.94	<0.01	20	1.39	552	<1	93	619	21	0.50	<5	<5	<10	283	3288	<2	100	<10	13	74
196607	1305920	1.999	<1	3.86	9	377	<2	5	2.48	4	19	52	36	4.09	<0.01	12	1.50	754	<1	37	680	9	0.43	6	<5	<10	291	3133	<2	128	22	17	64
196608	1305921	<0.005	<1	3.89	19	299	<2	3	1.76	<4	18	124	61	3.34	<0.01	17	1.26	489	<1	73	535	15	0.69	<5	<5	<10	235	2253	<2	70	<10	14	56
196609	1305922	0.006	<1	5.16	19	394	2	<1	1.86	<4	20	144	42	3.98	<0.01	22	1.52	601	<1	87	573	22	0.57	<5	<5	<10	294	2831	<2	90	<10	15	68
196610	1305923	0.005	<1	4.21	20	353	<2	<1	1.38	<4	19	133	38	3.64	<0.01	22	1.41	496	<1	79	543	17	0.52	<5	<5	<10	253	2677	<2	83	<10	14	54
196611D	1305923	<0.005	1	3.86	21	356	<2	6	1.34	<4	20	137	39	3.74	<0.01	22	1.42	503	<1	84	541	14	0.53	<5	<5	<10	248	2643	<2	83	<10	13	57
196612	1305924	0.008	<1	4.36	25	383	<2	5	1.11	<4	22	145	47	4.12	<0.01	26	1.57	504	<1	81	582	22	0.52	5	<5	<10	236	2874	<2	92	<10	14	77
196613	1305925	<0.005	<1	3.57	21	377	<2	3	0.97	<4	23	141	48	3.85	<0.01	23	1.48	469	<1	85	533	20	0.56	<5	<5	<10	220	2620	<2	85	<10	13	76
196614	1305926	<0.005	<1	2.44	20	377	<2	12	0.67	<4	22	139	50	3.79	<0.01	20	1.44	405	<1	86	532	20	0.52	<5	<5	<10	176	2426	2	81	<10	13	85
196615	1305927	0.012	<1	3.97	4	333	<2	<1	1.32	<4	16	134	40	3.10	<0.01	17	1.16	399	3	107	451	21	0.61	<5	<5	<10	291	2182	<2	67	<10	12	45
196616	1305928	0.023	1	6.25	<2	744	2	7	1.11	4	29	166	59	4.50	<0.01	32	1.61	484	<1	108	1020	21	0.99	<5	<5	<10	304	3317	<2	111	<10	14	87
196617	1305929	0.016	1	5.59	7	409	2	<1	1.74	4	20	149	66	4.20	<0.01	28	1.66	587	1	92	615	16	1.10	<5	<5	<10	358	2549	2	85	<10	14	78
196618	1305930	0.006	<1	5.59	9	469	2	<1	1.44	<4	22	153	49	4.06	<0.01	31	1.53	557	<1	102	611	18	0.70	<5	<5	<10	360	2852	<2	92	<10	14	61

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/04/2012
 Date Completed:
 Job #: 201242633
 Reference: TL 12 251
 Sample #: 222

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
196619	1305931	<0.005	<1	5.56	13	553	2	<1	1.33	<4	24	163	48	4.31	<0.01	31	1.58	543	2	113	674	26	0.57	<5	<5	<10	382	3372	2	105	<10	14	68
196620	1305932	0.011	<1	4.84	26	824	2	9	1.20	<4	22	149	43	3.70	<0.01	27	1.40	466	2	107	544	17	0.62	<5	<5	<10	351	2950	<2	94	<10	12	69
196621	1305933	0.008	<1	5.15	<2	694	2	5	1.49	<4	21	139	44	3.70	<0.01	26	1.46	520	<1	86	547	19	0.62	<5	<5	<10	384	2883	<2	85	<10	14	66
196622D	1305933	<0.005	<1	4.35	2	683	2	6	1.37	<4	20	143	44	3.74	<0.01	24	1.46	526	<1	94	541	16	0.55	<5	<5	<10	362	2794	<2	84	<10	13	69
196623	1305934	<0.005	<1	4.31	3	849	<2	2	1.39	<4	12	86	32	2.65	<0.01	19	1.05	336	<1	59	441	14	0.59	<5	<5	<10	350	2207	<2	58	<10	9	53
196624	1305935	0.009	<1	4.04	<2	955	2	1	1.17	<4	18	142	40	3.60	<0.01	29	1.33	391	5	120	562	10	0.59	<5	<5	<10	337	2711	<2	83	<10	11	62
196625	1305936	<0.005	<1	3.91	6	452	2	2	1.28	<4	23	152	46	4.16	<0.01	34	1.52	545	<1	96	530	18	0.60	<5	<5	<10	338	2728	<2	91	<10	11	73
196626	1305937	0.006	<1	4.00	4	480	<2	<1	1.31	<4	20	154	46	3.87	<0.01	29	1.46	501	1	103	556	24	0.61	<5	<5	<10	346	2654	3	83	<10	12	68
196627	1305938	0.006	<1	3.57	21	767	<2	5	1.15	<4	15	104	28	2.95	<0.01	20	1.20	376	<1	94	433	10	0.52	<5	<5	<10	264	2000	2	66	<10	10	48
196628	1305939	0.007	1	6.25	91	515	2	8	1.62	<4	22	149	43	3.95	<0.01	34	1.55	586	<1	97	562	20	0.64	<5	<5	<10	324	2821	<2	94	<10	15	63
196629	1305940	NS																															
196630	1305941	0.009	1	5.14	52	434	2	2	1.74	4	19	144	48	3.92	<0.01	31	1.42	601	<1	101	535	19	0.69	<5	<5	<10	308	2528	2	81	<10	15	62
196631	1305942	0.009	<1	5.30	57	500	2	6	1.44	<4	24	161	57	4.30	<0.01	36	1.50	590	<1	108	536	20	0.68	<5	<5	<10	276	2982	<2	97	<10	14	66
196632	1305943	0.007	1	4.65	84	482	<2	7	1.56	<4	20	152	44	3.49	<0.01	27	1.28	461	1	98	497	18	0.63	<5	<5	<10	275	2699	<2	78	<10	14	58
196633D	1305943	0.007	1	4.60	81	485	<2	9	1.56	<4	19	151	44	3.51	<0.01	29	1.26	461	1	98	496	20	0.67	<5	<5	<10	274	2733	<2	78	<10	13	59
196634	1305944	<0.005	1	4.14	38	579	<2	<1	1.85	<4	19	149	43	3.57	<0.01	31	1.32	543	1	95	499	17	0.68	<5	<5	<10	260	2622	<2	75	<10	13	59
196635	1305945	0.006	<1	3.99	23	531	<2	23	1.68	<4	17	132	47	3.09	<0.01	24	1.22	481	2	81	437	15	0.25	<5	5	<10	222	2296	<2	68	<10	12	103
196636	1305946	0.006	<1	3.13	15	539	<2	<1	1.93	<4	17	130	43	3.33	<0.01	27	1.30	516	<1	75	477	18	0.56	<5	<5	<10	224	2269	4	69	<10	14	76
196637	1305947	0.006	<1	3.85	18	428	<2	1	1.88	<4	19	151	48	3.65	<0.01	29	1.33	439	2	103	517	19	0.64	<5	<5	<10	239	2360	<2	73	<10	12	69
196638	1305948	0.009	<1	3.54	43	343	<2	3	1.57	<4	18	140	40	3.39	<0.01	27	1.21	446	1	90	481	16	0.63	<5	<5	<10	197	2185	2	69	<10	13	73

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/04/2012
 Date Completed:
 Job #: 201242633
 Reference: TL 12 251
 Sample #: 222

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
196639	1305949	0.007	<1	3.30	59	400	<2	5	1.68	4	21	138	49	4.30	<0.01	30	1.56	561	<1	101	548	18	0.52	<5	<5	<10	208	2193	<2	85	<10	15	68
196640	1305950	0.009	1	5.85	68	498	2	<1	1.54	<4	23	144	49	4.20	<0.01	48	1.61	525	<1	92	575	17	0.69	<5	<5	<10	222	2945	<2	96	<10	17	53
196641	1305951	0.010	<1	4.95	16	439	2	<1	1.75	4	22	143	54	4.01	<0.01	44	1.73	538	<1	95	542	15	0.71	<5	<5	<10	219	2592	2	85	<10	15	109
196642	1305952	0.007	1	4.95	2	428	2	4	1.62	<4	20	143	49	3.78	<0.01	51	1.58	519	2	100	549	12	0.67	8	<5	<10	211	2605	<2	83	<10	14	58
196643	1305953	<0.005	<1	4.07	<2	470	<2	14	1.18	<4	20	144	46	3.44	<0.01	45	1.35	436	2	99	522	18	0.66	<5	<5	<10	190	2263	<2	71	<10	13	54
196644R	1305953	0.009	1	5.14	5	488	2	<1	1.31	<4	19	145	43	3.35	<0.01	50	1.29	449	2	90	515	16	0.78	<5	<5	<10	208	2685	<2	77	<10	13	81
196645	1305954	<0.005	<1	4.03	3	527	<2	4	1.70	<4	14	108	35	2.88	<0.01	45	1.35	435	<1	81	452	19	0.52	<5	<5	<10	204	1986	<2	56	<10	11	61
196646	1305955	<0.005	1	5.46	<2	631	2	5	1.40	<4	7	39	16	1.62	<0.01	52	1.06	251	<1	50	342	14	0.52	5	<5	<10	214	1707	<2	36	<10	7	53
196647	1305956	0.010	<1	5.24	4	835	2	2	2.28	<4	9	62	34	2.13	<0.01	46	1.16	358	<1	42	396	9	0.71	<5	<5	<10	234	1815	4	47	<10	9	34
196648	1305957	0.006	<1	5.47	6	589	<2	<1	1.46	<4	5	27	8	1.38	<0.01	41	0.74	241	<1	43	320	6	0.53	<5	<5	<10	203	1486	<2	29	<10	5	28
196649	1305958	<0.005	<1	5.02	7	623	<2	<1	1.61	<4	5	18	6	1.32	<0.01	34	0.61	184	<1	34	311	7	0.55	5	<5	<10	210	1388	<2	28	<10	5	33
196650	1305959	0.008	<1	4.76	14	526	<2	1	1.97	<4	5	20	6	1.35	<0.01	27	0.60	160	<1	35	322	5	0.49	<5	<5	<10	184	1379	<2	27	<10	5	27
196651	1305960	0.242	1	0.90	426	>5000	<2	11	1.06	<4	4	12	32	2.87	0.04	8	0.32	<100	7	16	110	18	0.94	21	<5	<10	155	959	<2	17	46	10	20
196652	1305961	0.007	1	4.82	381	431	2	10	1.83	8	14	137	569	2.51	<0.01	40	1.12	248	3	83	525	235	0.67	<5	<5	33	216	2562	2	86	27	13	1929
196653	1305962	<0.005	1	3.44	70	298	<2	<1	3.07	<4	16	145	1	2.85	<0.01	36	1.22	416	<1	84	487	8	0.44	<5	<5	<10	216	2410	<2	82	<10	10	17
196654	1305963	0.015	1	4.14	887	243	<2	4	3.63	6	49	51	74	7.38	0.10	37	1.63	1158	<1	82	889	5	1.12	<5	<5	<10	194	3802	<2	320	<10	30	44
196655D	1305963	0.013	1	4.17	955	254	<2	3	3.78	7	53	53	81	7.91	0.11	41	1.63	1250	<1	86	937	9	1.26	<5	<5	<10	203	4376	<2	348	<10	28	49
196656	1305964	0.023	1	5.58	44	182	<2	7	4.13	7	53	39	86	8.06	<0.01	64	1.70	1377	<1	74	1732	9	1.11	5	<5	<10	198	5529	4	355	<10	47	46
196657	1305965	0.008	1	5.45	8	316	<2	4	5.03	10	57	39	98	10.46	<0.01	51	2.22	1803	<1	67	888	13	1.10	<5	<5	<10	198	6803	<2	352	<10	43	106
196658	1305966	<0.005	1	5.17	6	338	<2	11	4.98	10	58	34	104	10.74	<0.01	53	2.18	1845	<1	62	868	16	1.14	<5	<5	<10	202	7513	11	370	<10	38	115

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/04/2012
 Date Completed:
 Job #: 201242633
 Reference: TL 12 251
 Sample #: 222

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
196659	1305967	0.023	2	5.83	8	277	<2	14	5.84	10	60	40	129	11.33	<0.01	42	2.33	2096	<1	62	1065	21	1.64	<5	<5	<10	244	7338	5	343	<10	43	104
196660	1305968	<0.005	1	3.36	<2	147	<2	3	4.30	8	44	54	112	8.20	<0.01	29	1.88	1407	<1	57	669	7	1.17	<5	<5	<10	169	4570	2	242	<10	31	101
196661	1305969	0.006	1	4.89	9	134	<2	8	5.27	9	48	55	105	9.73	<0.01	30	2.49	1545	<1	57	725	13	0.86	<5	<5	<10	203	5301	5	290	<10	37	137
196662	1305970	0.007	1	4.59	<2	139	<2	15	6.02	9	52	60	133	9.37	0.04	35	2.29	1378	<1	64	789	11	0.73	<5	<5	<10	221	5982	<2	327	<10	35	87
196663	1305971	<0.005	1	4.20	3	174	<2	16	6.00	10	54	61	105	10.65	0.09	51	2.40	1584	<1	61	758	9	0.80	<5	<5	<10	208	5675	3	337	<10	35	101
196664	1305972	0.013	1	3.41	7	105	<2	14	5.43	10	55	63	125	10.61	0.05	43	2.29	1869	<1	64	765	12	1.02	<5	<5	<10	198	4623	4	331	<10	34	130
196665	1305973	<0.005	1	2.92	2	193	<2	4	5.08	10	46	56	94	10.83	0.06	42	1.98	2474	<1	62	680	25	0.98	<5	<5	<10	181	5191	12	302	<10	29	162
196666D	1305973	<0.005	2	4.13	<2	227	<2	17	5.76	12	54	66	105	12.22	0.23	50	2.18	2846	<1	74	755	20	1.12	<5	<5	<10	209	6440	3	341	<10	32	183
196667	1305974	<0.005	1	4.24	4	517	<2	8	4.69	8	56	64	141	9.09	0.14	53	2.08	2054	<1	66	781	38	1.12	<5	<5	<10	203	5583	2	331	<10	33	173
196668	1305975	0.008	2	5.81	8	146	<2	1	4.94	9	54	70	125	9.88	<0.01	55	2.92	2159	<1	70	923	15	0.88	<5	<5	<10	191	5748	10	351	<10	44	114
196669	1305976	<0.005	1	5.13	6	73	<2	4	4.77	9	49	62	135	9.25	<0.01	44	2.72	2062	<1	64	762	14	1.03	<5	<5	<10	176	5868	4	304	<10	38	92
196670	1305977	0.017	2	5.38	<2	169	<2	6	5.44	10	62	77	148	10.49	<0.01	56	2.35	2427	<1	86	917	24	1.51	<5	<5	<10	215	7823	<2	354	<10	37	88
196671	1305978	0.039	3	5.64	10	209	<2	18	4.41	12	60	51	225	11.86	<0.01	55	2.16	2125	<1	90	773	52	4.35	<5	<5	<10	165	5252	<2	269	<10	32	271
196672	1305979	0.037	2	4.21	9	239	3	6	3.40	9	42	43	103	8.09	<0.01	58	1.66	1997	<1	66	766	23	2.18	<5	<5	<10	133	5933	5	302	<10	33	164
196673	1305980	0.007	1	4.81	7	386	<2	<1	2.64	<4	18	48	28	3.66	0.03	15	1.42	750	<1	34	627	10	0.58	<5	<5	<10	314	3275	<2	125	20	17	53
196674	1305981	0.018	3	6.62	2	327	2	<1	3.92	8	59	50	164	8.28	0.32	88	1.87	1546	<1	76	1014	30	2.61	<5	<5	<10	180	8148	5	395	12	32	170
196675	1305982	0.014	2	4.97	<2	229	<2	12	4.78	8	50	41	93	8.29	0.14	53	1.99	2723	<1	72	952	36	1.42	<5	<5	<10	188	6527	<2	349	<10	37	169
196676	1305983	0.021	2	4.75	<2	79	<2	4	4.70	10	57	31	104	10.42	0.21	61	2.67	3167	<1	61	878	24	1.54	<5	<5	<10	167	5099	<2	347	<10	39	192
196677D	1305983	0.026	2	4.51	<2	79	<2	3	4.64	10	58	33	101	10.37	0.19	61	2.57	3252	<1	62	862	22	1.53	<5	<5	<10	166	5826	14	348	<10	37	189
196678	1305984	0.039	3	5.46	4	157	<2	8	5.74	10	52	32	209	10.35	0.14	85	2.22	3182	<1	60	940	23	1.26	<5	<5	<10	175	6530	2	360	<10	42	160

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/04/2012
 Date Completed:
 Job #: 201242633
 Reference: TL 12 251
 Sample #: 222

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
196679	1305985	0.009	2	5.20	11	112	<2	2	5.27	9	54	33	97	9.41	0.21	40	2.66	2363	<1	59	913	11	0.86	<5	<5	<10	165	5650	2	366	<10	43	149
196680	1305986	0.016	2	7.11	10	87	<2	16	5.78	9	61	38	91	10.16	<0.01	41	2.94	2577	<1	68	979	15	0.99	<5	<5	<10	180	7313	3	383	<10	49	150
196681	1305987	0.017	2	5.19	3	5	<2	9	4.71	9	52	37	103	9.03	<0.01	37	2.49	1993	<1	57	732	57	1.00	<5	<5	<10	151	6191	<2	310	<10	40	192
196682	1305988	0.008	2	6.69	<2	14	<2	6	5.21	10	56	38	120	10.22	<0.01	45	2.87	2508	<1	61	860	25	1.03	6	<5	<10	184	7382	<2	352	<10	42	219
196683	1305989	0.009	2	5.99	5	<1	<2	7	5.48	9	57	39	106	10.27	<0.01	44	2.52	2342	<1	62	803	9	0.92	<5	<5	<10	176	7404	<2	340	<10	41	149
196684	1305990	0.010	1	2.70	10	126	<2	8	6.31	8	55	35	97	8.78	<0.01	32	1.94	2389	<1	61	886	18	0.72	<5	<5	<10	171	3529	2	321	<10	41	125
196685	1305991	0.014	3	4.52	12	<1	<2	7	6.08	14	53	45	189	10.83	0.11	36	2.00	2712	<1	58	813	31	1.86	<5	<5	<10	150	4306	4	287	10	40	961
196686	1305992	0.024	2	5.03	7	70	<2	6	4.43	10	50	47	121	9.42	0.09	50	2.86	2642	<1	54	791	25	0.79	<5	<5	<10	163	5829	5	307	<10	43	366
196687	1305993	0.035	2	4.42	7	143	<2	7	5.94	9	53	58	128	9.97	0.15	48	2.11	2696	<1	63	780	22	1.15	<5	<5	<10	159	6483	2	312	<10	38	179
196688D	1305993	0.014	2	2.79	4	141	<2	5	5.84	9	52	55	129	9.93	0.17	49	1.89	2702	<1	65	752	26	1.19	<5	<5	<10	155	6211	4	314	<10	30	181
196689	1305994	0.132	3	3.13	2	153	<2	6	4.52	38	57	65	156	10.63	0.19	56	1.82	2930	<1	72	754	46	2.17	<5	<5	<10	136	5165	<2	314	42	29	4926
196690	1305995	0.905	3	3.14	3	120	<2	10	2.66	25	56	57	222	9.50	0.16	55	1.73	2736	<1	67	723	258	1.77	5	<5	<10	114	4289	<2	296	31	26	3186
196691	1305996	0.020	2	3.45	3	119	<2	10	4.18	10	51	75	135	9.12	0.16	39	1.78	2593	<1	84	765	33	0.99	<5	<5	<10	134	4330	<2	322	<10	33	438
196692	1305997	0.045	2	6.19	3	47	<2	6	6.10	10	55	66	115	10.28	<0.01	31	2.33	2287	<1	66	839	25	1.04	5	<5	<10	193	5938	<2	344	<10	42	148
196693	1305998	0.013	2	6.78	2	56	<2	12	6.77	10	63	67	108	11.02	<0.01	35	2.35	2242	<1	65	917	29	1.11	<5	<5	<10	213	7427	6	342	<10	42	148
196694	1305999	0.012	2	6.19	4	134	<2	18	5.95	10	58	71	100	10.86	<0.01	52	2.23	3541	<1	72	856	28	1.11	<5	<5	<10	194	6880	3	349	<10	42	213
196695	1306000	5.234	60	5.03	43	458	<2	1	1.74	22	15	33	57	3.55	<0.01	14	1.05	591	<1	27	597	582	0.92	72	<5	238	278	2383	<2	102	57	17	1909
196696	1361501	0.066	4	5.64	<2	170	<2	3	3.38	11	55	67	140	9.54	<0.01	63	1.80	3521	<1	74	793	235	1.81	<5	<5	10	140	6738	4	324	14	31	838
196697	1361502	0.046	2	4.94	7	95	<2	9	4.05	11	66	66	160	11.48	0.01	65	1.93	3010	<1	80	747	46	2.12	5	<5	<10	146	6694	7	341	<10	30	342
196698	1361503	0.024	2	4.78	2	113	<2	6	4.05	9	62	74	114	9.67	0.13	53	1.78	3037	<1	90	789	26	1.23	<5	<5	<10	158	5882	<2	356	<10	33	188

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/04/2012
 Date Completed:
 Job #: 201242633
 Reference: TL 12 251
 Sample #: 222

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
196699D	1361503	0.049	2	5.03	<2	118	<2	12	4.11	9	63	73	114	9.81	0.15	53	1.79	3120	<1	89	789	30	1.23	<5	<5	<10	162	6786	2	365	<10	33	189
196700	1361504	0.017	2	4.49	11	124	<2	6	5.70	11	79	81	159	12.31	0.16	51	1.92	2584	<1	95	926	35	1.69	<5	<5	<10	175	5882	<2	398	<10	33	205
196701	1361505	<0.005	2	3.82	<2	86	<2	10	4.61	9	63	73	114	9.80	0.08	35	1.73	2172	<1	83	818	26	1.12	<5	<5	<10	169	6178	<2	370	<10	31	147
196702	1361506	0.009	2	4.12	<2	93	<2	12	4.43	9	62	70	115	9.53	0.16	35	1.73	2082	<1	83	810	28	1.12	<5	<5	<10	171	6087	<2	362	<10	32	143
196703	1361507	0.047	2	4.45	<2	146	<2	1	5.29	10	66	73	125	10.68	0.15	43	1.90	2302	<1	85	894	35	1.44	<5	<5	<10	188	5495	2	377	<10	36	178
196704	1361508	0.007	2	7.45	<2	106	<2	10	5.48	11	62	75	139	11.62	<0.01	52	2.52	2360	<1	74	1058	31	1.51	<5	<5	<10	216	6702	<2	399	<10	46	212
196705	1361509	0.600	3	5.99	8	210	<2	2	1.69	11	68	74	295	10.59	<0.01	56	1.44	921	<1	90	756	66	4.94	<5	<5	<10	136	5814	2	317	13	28	718
196706	1361510	0.052	2	7.59	3	129	<2	5	4.59	11	57	71	134	11.80	<0.01	62	2.89	1671	<1	63	892	36	1.47	<5	<5	<10	174	7074	<2	366	13	46	183
196707	1361511	0.006	2	6.05	3	77	<2	12	5.93	10	58	68	118	10.65	<0.01	37	2.42	2062	<1	66	856	21	1.06	<5	<5	<10	233	6761	4	357	<10	38	172
196708	1361512	0.014	2	5.81	3	29	<2	11	6.03	10	55	75	111	10.88	0.07	35	2.65	1862	<1	77	869	20	0.80	<5	<5	<10	197	6191	<2	335	10	40	167
196709	1361513	0.005	2	7.01	54	7	<2	13	6.09	12	58	66	187	10.91	0.03	48	2.69	1750	<1	67	842	57	0.91	<5	<5	10	251	7141	2	342	13	38	550
196710R	1361513	0.006	2	6.27	11	3	<2	6	6.39	10	57	64	124	11.07	<0.01	44	2.73	1870	<1	66	830	34	0.83	<5	<5	<10	241	6888	4	345	10	38	233
196711	1361514	<0.005	2	6.07	7	<1	<2	2	5.94	10	56	65	126	11.29	<0.01	28	2.49	2181	<1	61	822	17	0.90	<5	<5	<10	230	6685	4	358	<10	38	178
196712	1361515	0.074	2	5.94	9	146	<2	13	6.27	11	50	60	101	11.72	<0.01	35	2.53	2920	<1	60	778	29	1.13	6	<5	<10	185	6614	6	313	<10	39	151
196713	1361516	0.012	2	5.00	5	99	<2	5	5.58	8	53	60	114	8.58	<0.01	24	2.12	1969	<1	62	852	25	0.90	<5	<5	<10	179	6783	<2	334	<10	35	135
196714	1361517	0.039	3	5.14	6	178	<2	4	3.70	13	53	70	158	8.26	0.02	39	1.84	1727	<1	66	836	193	1.89	<5	<5	<10	160	7177	<2	331	13	28	972
196715	1361518	0.018	2	5.16	<2	99	<2	4	4.12	9	50	64	107	9.41	0.09	46	2.44	1991	<1	65	837	61	1.39	<5	<5	<10	158	5694	4	328	11	36	230
196716	1361519	0.026	2	3.39	12	47	<2	7	3.19	10	41	75	158	9.99	0.09	36	1.92	1752	<1	65	552	28	1.88	<5	7	<10	124	4859	5	260	<10	25	201
196717	1361520	0.005	<1	3.91	9	367	<2	7	2.55	<4	17	52	28	3.71	<0.01	9	1.50	738	<1	35	635	9	0.46	6	<5	<10	291	3035	<2	123	23	18	62
196718	1361521	0.042	2	4.18	10	244	2	9	2.74	10	60	67	138	10.67	<0.01	67	2.02	1858	<1	76	950	42	2.08	5	<5	<10	125	4914	<2	365	10	27	184

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/04/2012
 Date Completed:
 Job #: 201242633
 Reference: TL 12 251
 Sample #: 222

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
196719	1361522	0.332	3	4.21	15	99	<2	11	2.60	12	50	63	156	12.17	0.10	61	2.47	2233	<1	77	787	52	2.88	5	<5	<10	111	4207	<2	286	20	27	211
196720	1361523	0.103	2	3.90	20	204	<2	13	2.77	11	50	62	90	11.29	0.03	58	2.17	2037	<1	72	828	102	2.05	<5	<5	<10	151	4006	<2	311	<10	24	275
196721D	1361523	0.102	2	4.51	18	213	<2	13	2.94	12	56	67	93	12.16	<0.01	58	2.40	2375	<1	72	889	112	2.09	<5	<5	<10	153	6270	18	350	<10	29	292
196722	1361524	0.433	3	5.47	19	328	<2	9	1.91	9	47	69	150	9.64	<0.01	60	1.52	1385	<1	95	904	61	3.90	6	<5	<10	120	6729	<2	348	17	19	210
196723	1361525	1.336	4	5.07	34	131	<2	8	2.75	10	47	66	231	10.27	<0.01	57	1.85	1903	<1	92	871	46	4.08	<5	<5	<10	124	7463	4	336	16	24	227
196724	1361526	2.628	3	3.95	36	122	<2	6	2.38	9	42	62	138	9.42	<0.01	56	1.93	1664	<1	81	907	51	3.43	<5	<5	<10	107	5339	<2	316	13	24	235
196725	1361527	0.194	2	5.22	26	82	<2	9	2.83	11	54	57	121	11.16	<0.01	66	2.31	1671	<1	72	843	50	2.45	<5	<5	<10	112	5380	7	332	14	24	209
196726	1361528	0.041	2	4.91	18	81	<2	14	4.41	10	50	58	98	10.75	0.05	53	2.50	1953	<1	69	918	45	1.42	<5	<5	<10	161	5392	2	334	14	34	179
196727	1361529	0.031	2	4.90	9	103	<2	8	4.17	10	59	56	128	10.72	0.03	53	2.38	1821	<1	67	866	37	1.61	<5	<5	<10	161	5957	<2	331	10	36	183
196728	1361530	0.110	2	3.92	25	170	<2	11	4.10	9	52	45	147	9.79	0.12	41	1.92	2386	<1	64	805	35	2.86	<5	<5	<10	153	6706	<2	305	<10	33	271
196729	1361531	0.365	3	3.61	26	175	<2	6	2.05	9	47	34	189	9.26	0.08	50	1.55	1937	<1	62	856	154	3.54	<5	<5	<10	109	5670	<2	311	12	28	391
196730	1361532	0.190	3	3.52	22	259	<2	<1	1.73	6	44	57	109	6.52	0.02	40	1.44	1225	3	70	646	48	1.90	<5	<5	<10	106	3383	<2	179	<10	16	222
196731	1361533	0.107	2	4.25	13	279	<2	7	2.97	9	42	61	117	8.53	0.04	67	2.00	1449	<1	76	897	47	2.04	<5	<5	<10	125	5155	3	291	10	30	550
196732D	1361533	0.098	2	4.50	19	282	<2	4	3.08	9	43	68	119	8.71	0.09	68	2.04	1489	1	80	932	49	2.09	<5	<5	<10	128	5338	11	297	11	31	560
196733	1361534	0.034	2	6.14	60	194	<2	6	4.58	11	54	56	128	10.40	<0.01	57	2.35	2360	<1	71	1009	58	1.06	5	<5	<10	136	7819	<2	351	<10	42	258
196734	1361535	0.014	2	6.22	21	163	<2	14	5.46	11	61	60	165	11.42	<0.01	41	2.34	2792	<1	66	1069	30	1.28	6	5	<10	162	9039	2	383	13	45	246
196735	1361536	0.009	2	6.53	14	238	<2	10	4.84	8	46	58	98	8.39	<0.01	39	1.84	2171	<1	67	809	15	1.17	<5	<5	<10	182	7444	6	256	<10	26	247
196736	1361537	0.011	2	4.20	21	5	<2	12	5.06	9	45	64	93	9.61	<0.01	17	1.94	2097	<1	86	737	17	1.11	<5	<5	<10	136	5558	5	251	<10	35	179
196737	1361538	0.013	2	5.94	8	6	<2	7	6.48	11	57	53	109	11.91	<0.01	28	2.37	2456	<1	66	878	26	1.41	<5	<5	<10	165	6363	7	336	<10	39	193
196738	1361539	0.028	2	4.93	58	62	<2	17	6.57	10	52	60	145	10.76	0.04	26	1.90	2583	<1	71	893	22	1.35	5	<5	<10	164	6706	<2	327	<10	34	286

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/04/2012
 Date Completed:
 Job #: 201242633
 Reference: TL 12 251
 Sample #: 222

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
196739	1361540	1.888	1	5.33	12	411	<2	7	2.68	<4	18	51	36	3.99	0.06	15	1.50	784	<1	38	660	7	0.58	7	<5	<10	306	3230	2	129	27	17	67
196740	1361541	0.077	2	3.93	12	8	<2	11	5.57	10	50	52	86	11.22	0.12	29	2.35	2315	<1	63	855	25	0.98	<5	<5	<10	170	6073	4	323	<10	33	161
196741	1361542	0.046	2	4.02	161	175	<2	16	6.07	11	55	50	126	11.17	0.21	45	2.41	2088	<1	62	895	24	0.98	<5	<5	<10	183	6582	<2	355	<10	32	243
196742	1361543	0.038	2	5.38	23	88	<2	12	6.43	11	55	68	119	11.30	0.18	39	2.86	1736	<1	67	936	24	0.86	<5	<5	<10	183	6027	<2	354	<10	40	178
196743D	1361543	0.046	2	4.86	11	87	<2	18	6.21	10	56	66	115	11.00	0.19	39	2.61	1713	<1	66	898	20	0.93	<5	<5	<10	186	6883	5	354	<10	34	170
196744	1361544	0.058	2	5.98	213	305	<2	19	5.72	11	60	73	149	11.81	0.23	68	3.06	2159	<1	71	954	28	2.05	5	<5	<10	161	6563	<2	359	13	37	279
196745	1361545	0.030	2	6.81	23	74	<2	11	6.91	11	61	78	135	12.07	<0.01	42	3.06	1957	<1	78	996	20	1.10	<5	<5	<10	195	6956	2	304	<10	46	186
196746	1361546	0.022	2	6.49	9	106	<2	18	6.86	11	60	82	128	12.23	<0.01	43	3.09	2040	<1	86	981	24	0.95	6	<5	<10	186	8118	10	310	<10	44	184
196747	1361547	0.011	1	6.18	9	6	<2	11	7.10	11	61	53	113	11.56	<0.01	32	2.72	1788	<1	94	882	27	0.81	<5	<5	<10	197	7655	8	310	<10	40	165
196748	1361548	0.005	2	5.48	5	82	<2	7	6.84	10	64	50	109	10.71	<0.01	34	2.24	2031	<1	92	881	22	0.91	<5	<5	<10	192	8450	7	321	<10	32	147
196749	1361549	0.005	2	6.06	<2	124	<2	2	6.54	10	65	57	137	10.69	<0.01	37	2.29	2035	<1	83	881	19	0.96	5	<5	<10	165	7831	6	351	<10	37	146
196750	1361550	0.016	2	5.56	21	159	<2	5	5.17	8	57	56	131	9.06	0.05	49	2.12	1989	<1	79	890	17	1.01	<5	<5	<10	174	7111	4	337	<10	35	127
196751	1361551	0.146	2	4.52	64	127	2	11	5.33	32	53	42	137	9.46	0.10	50	1.99	2087	<1	81	858	20	2.21	<5	<5	<10	171	6590	3	329	37	35	4188
196752	1361552	0.025	2	4.05	14	87	<2	8	5.62	10	50	29	152	10.36	0.21	42	1.96	1882	<1	69	914	18	1.05	<5	<5	<10	159	6305	3	351	<10	40	265
196753	1361553	0.006	2	3.96	12	80	<2	4	5.56	9	49	31	111	10.08	0.17	41	2.08	1712	<1	72	930	26	1.00	<5	<5	<10	158	6063	<2	347	<10	40	174
196754D	1361553	0.010	2	3.99	13	80	<2	7	5.52	9	51	26	109	9.99	0.11	42	2.09	1688	<1	62	929	21	0.98	<5	<5	<10	155	5983	<2	346	<10	40	168
196755	1361554	0.055	2	4.28	204	158	<2	9	4.24	11	48	33	90	8.82	0.10	61	2.08	1770	<1	75	966	28	1.47	<5	<5	<10	158	5777	15	347	<10	37	587
196756	1361555	0.033	2	3.96	9	121	<2	10	5.30	11	46	36	119	10.34	0.10	57	2.27	2470	<1	73	867	29	1.89	<5	<5	<10	140	5597	4	304	13	41	609
196757	1361556	0.054	2	5.38	3	167	<2	13	5.80	15	49	53	95	9.51	<0.01	51	2.66	2466	<1	69	988	17	0.94	7	<5	<10	157	6668	3	326	18	52	1110
196758	1361557	0.049	2	5.09	2	200	<2	<1	5.57	9	54	62	126	9.39	<0.01	52	2.26	2416	<1	69	959	18	1.17	<5	<5	<10	166	7407	<2	332	<10	46	289

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/04/2012
 Date Completed:
 Job #: 201242633
 Reference: TL 12 251
 Sample #: 222

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
196759	1361558	0.030	2	5.96	6	178	<2	13	6.67	8	63	88	132	9.14	<0.01	52	1.97	2166	<1	89	1048	11	1.08	<5	<5	<10	176	7692	<2	369	<10	44	200
196760	1361559	0.010	1	5.15	12	139	<2	10	5.22	9	63	73	113	9.23	<0.01	46	2.29	1822	<1	93	904	9	0.89	<5	<5	<10	172	6876	11	301	<10	38	158
196761	1361560	0.006	<1	3.62	5	331	<2	2	2.46	<4	18	48	25	3.51	<0.01	9	1.45	705	<1	33	634	7	0.43	<5	<5	<10	277	3032	<2	118	19	18	55
196762	1361561	0.010	2	5.27	4	120	<2	22	5.89	8	59	61	84	9.30	<0.01	38	2.10	2463	<1	96	879	11	0.91	5	<5	<10	198	6570	6	331	<10	37	245
196763	1361562	0.064	2	4.70	8	66	<2	18	4.73	9	48	30	148	9.44	0.02	35	1.98	1882	<1	73	895	17	1.65	<5	<5	<10	165	5850	5	314	<10	45	198
196764	1361563	0.008	1	3.88	10	57	<2	8	5.87	10	50	27	124	10.95	0.06	41	2.40	1918	<1	62	939	11	0.94	<5	<5	<10	166	5165	10	345	<10	45	196
196765D	1361563	0.010	2	4.14	2	59	3	17	5.89	11	52	23	121	10.88	0.19	42	2.41	1889	<1	58	933	13	0.93	<5	<5	<10	170	5157	2	344	<10	47	199
196766	1361564	<0.005	1	3.80	7	89	<2	5	5.71	8	45	27	98	9.23	0.15	51	2.05	1740	<1	59	953	13	0.79	<5	<5	<10	142	4893	2	311	<10	41	139
196767	1361565	0.011	1	3.69	6	86	<2	3	4.50	8	43	22	124	8.89	0.07	64	2.04	1862	<1	56	935	19	1.04	<5	<5	<10	148	4662	3	339	<10	40	136
196768	1361566	0.010	1	3.97	<2	89	<2	10	4.70	8	45	28	120	9.15	0.09	63	2.13	1935	<1	68	983	20	1.01	5	<5	<10	149	4239	3	342	10	44	136
196769	1361567	0.055	2	5.21	<2	90	<2	15	4.94	11	54	33	150	11.07	<0.01	76	2.73	2329	<1	75	1006	48	1.89	<5	<5	<10	155	5793	5	373	<10	51	286
196770	1361568	0.047	1	5.39	4	131	<2	8	5.73	11	55	30	120	9.95	<0.01	74	2.32	2310	<1	72	1061	41	1.16	<5	<5	<10	171	6336	8	373	<10	51	589
196771	1361569	0.025	2	5.64	2	85	<2	9	4.96	10	52	29	127	10.71	<0.01	95	2.57	2474	<1	61	961	27	1.14	<5	<5	<10	162	6295	5	340	10	49	377
196772	1361570	0.051	2	4.50	<2	62	<2	11	5.48	15	44	52	123	11.48	<0.01	55	2.58	2742	<1	72	805	18	1.80	<5	<5	<10	150	5611	3	283	11	45	858
196773	1361571	0.011	1	5.06	11	77	<2	4	6.12	10	51	54	110	10.32	<0.01	57	2.68	2176	<1	78	926	18	0.70	<5	<5	<10	177	6547	9	321	<10	48	191
196774	1361572	0.006	1	1.75	3	77	<2	13	5.08	10	45	39	118	9.88	<0.01	48	2.29	2134	<1	57	788	10	0.60	<5	<5	<10	151	5388	<2	288	<10	41	197
196775	1361573	0.006	1	3.68	4	22	<2	2	5.85	9	48	40	108	9.32	<0.01	38	2.60	1551	<1	58	943	9	0.65	<5	<5	<10	204	4964	7	296	<10	48	145
196776R	1361573	0.006	1	5.08	3	35	<2	9	6.25	9	50	43	114	9.99	<0.01	44	2.70	1651	<1	61	945	12	0.73	<5	<5	<10	234	6425	8	326	<10	50	151
196777	1361574	0.009	<1	3.72	2	36	<2	12	5.38	9	47	29	119	9.70	<0.01	44	2.50	1747	<1	59	1044	5	0.82	5	<5	<10	210	5872	10	317	<10	51	161
196778	1361575	0.010	1	5.38	<2	11	<2	18	5.37	9	47	38	112	9.62	<0.01	51	2.59	1623	<1	58	951	2	0.77	<5	<5	<10	211	6774	4	334	<10	49	152

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/04/2012
 Date Completed:
 Job #: 201242633
 Reference: TL 12 251
 Sample #: 222

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
196779	1361576	0.217	1	5.58	16	<1	9	10	4.99	7	31	37	80	6.99	<0.01	89	2.02	1486	<1	54	1014	9	0.57	<5	<5	<10	184	4848	10	241	<10	37	93
196780	1361577	0.008	1	4.63	4	29	2	7	5.00	8	48	53	102	8.98	<0.01	83	2.61	1599	<1	65	863	6	0.66	<5	<5	<10	161	6033	5	302	<10	45	154
196781	1361578	0.008	1	3.63	11	40	<2	8	4.88	9	42	74	92	9.52	<0.01	59	2.39	1952	<1	83	773	7	0.83	<5	<5	<10	119	5032	8	243	<10	36	152
196782	1361579	0.006	1	3.95	<2	96	<2	<1	6.56	8	42	64	94	8.72	<0.01	47	2.26	1819	<1	64	911	5	0.69	<5	<5	<10	147	6390	2	256	<10	43	111
196783	1361580	0.244	1	0.24	460	4638	<2	2	1.05	<4	5	14	34	3.05	<0.01	5	0.31	<100	7	18	102	22	1.03	19	<5	<10	149	1027	2	18	55	10	22
196784	1361581	0.012	1	2.30	2	170	<2	5	5.22	8	41	54	90	9.08	0.01	54	2.31	1280	<1	67	956	4	1.01	7	<5	<10	158	3462	4	279	<10	47	141
196785	1361582	0.010	1	4.53	<2	158	<2	9	5.22	9	48	61	185	9.94	0.07	86	2.57	1420	<1	67	1013	14	1.59	<5	<5	<10	221	4994	<2	306	<10	46	144
196786	1361583	0.080	1	4.06	2	239	<2	8	5.88	8	42	64	260	8.92	0.16	82	2.53	1602	<1	65	672	13	1.40	<5	<5	<10	231	4882	3	272	24	39	141
196787D	1361583	0.048	1	3.95	7	207	<2	16	5.61	8	40	64	240	8.51	<0.01	76	2.49	1586	<1	71	636	10	1.29	<5	<5	<10	221	5709	6	257	28	40	132
196788	1361584	0.112	1	5.87	6	406	<2	16	6.95	10	50	83	185	10.56	<0.01	102	2.99	2164	<1	80	887	18	1.66	<5	<5	<10	239	6589	3	312	16	44	168
196789	1361585	0.020	1	5.23	<2	472	<2	4	5.16	9	52	64	108	9.40	<0.01	121	2.60	1862	<1	75	1046	11	1.50	<5	<5	<10	211	7693	<2	343	14	50	166
196790	1361586	0.027	2	5.98	2	433	<2	9	5.08	9	52	66	105	9.42	<0.01	124	2.59	1881	<1	78	1027	15	1.59	<5	<5	<10	213	8052	<2	337	12	51	164
196791	1361587	0.020	1	5.81	<2	187	<2	8	5.22	9	47	55	89	9.55	<0.01	92	2.72	1552	<1	59	1016	13	1.17	<5	<5	<10	237	6458	6	301	<10	51	154
196792	1361588	0.011	1	5.24	6	204	<2	5	4.93	8	44	64	85	8.51	<0.01	86	2.58	1516	<1	61	912	10	0.86	<5	<5	<10	197	6080	<2	283	<10	43	132
196793	1361589	0.008	1	4.07	<2	101	<2	11	4.86	8	42	65	78	8.72	<0.01	71	2.75	1294	<1	57	820	8	0.69	<5	<5	<10	173	4998	2	265	<10	35	114
196794	1361590	0.008	1	4.61	6	26	2	7	4.61	9	46	68	111	9.52	<0.01	78	3.02	1253	<1	64	858	6	0.75	<5	<5	<10	183	5875	6	299	<10	37	112
196795	1361591	0.007	1	4.06	2	<1	<2	10	5.21	10	49	45	111	10.76	0.08	88	3.08	1488	<1	67	978	10	0.74	<5	<5	<10	168	5310	<2	341	<10	40	144
196796	1361592	0.012	1	4.07	6	78	<2	12	6.49	9	49	93	129	9.68	0.12	60	2.52	1651	<1	75	791	11	0.74	7	<5	<10	205	6034	9	310	12	34	144
196797	1361593	0.017	<1	3.58	<2	138	<2	9	4.94	7	46	97	165	7.69	<0.01	72	2.42	1265	<1	72	794	5	0.67	<5	<5	<10	148	5206	2	268	<10	32	137
196798D	1361593	0.014	2	4.61	9	148	<2	3	5.45	8	51	103	186	8.32	<0.01	82	2.74	1370	<1	73	889	9	0.65	7	<5	<10	161	5916	<2	285	<10	38	151

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/04/2012
 Date Completed:
 Job #: 201242633
 Reference: TL 12 251
 Sample #: 222

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
196799	1361594	0.008	<1	4.71	<2	48	<2	8	6.08	7	47	97	127	7.80	<0.01	51	2.67	1475	<1	74	743	5	0.56	<5	<5	<10	205	6225	5	281	<10	34	123
196800	1361595	0.018	1	5.65	4	<1	<2	12	6.30	8	50	96	125	8.71	<0.01	67	2.90	1721	<1	73	807	5	0.65	<5	<5	<10	251	6854	3	312	10	36	131
196801	1361596	0.009	1	5.66	<2	67	<2	<1	5.92	8	45	80	105	8.42	<0.01	66	2.65	1638	<1	67	867	5	0.63	<5	<5	<10	212	6877	8	300	<10	39	135
196802	1361597	0.008	1	6.01	5	22	<2	8	5.64	9	52	82	122	9.87	<0.01	79	2.92	1657	<1	73	836	7	0.80	<5	<5	<10	164	7166	3	324	<10	38	163
196803	1361598	0.008	1	5.28	5	13	<2	6	6.46	8	47	90	129	8.83	<0.01	72	2.76	1928	<1	79	833	7	0.70	<5	<5	<10	172	6712	2	306	<10	38	138
196804	1361599	0.012	1	5.49	12	15	3	9	5.23	8	46	68	97	8.62	<0.01	98	2.67	1456	<1	75	799	6	0.64	<5	<5	<10	239	6070	9	272	<10	35	143
196805	1361600	0.009	<1	5.26	10	380	<2	<1	2.79	4	19	52	27	3.74	<0.01	14	1.58	747	<1	36	654	8	0.51	6	<5	<10	313	3326	4	127	22	19	58
196806	1361601	0.010	1	4.16	<2	17	<2	16	5.38	8	51	80	117	8.65	0.03	71	2.31	1476	<1	71	868	10	0.68	6	<5	<10	193	5982	2	322	<10	31	208
196807	1361602	0.012	1	3.88	3	34	<2	8	5.73	9	47	74	122	9.76	0.09	89	2.63	1469	<1	65	872	10	0.68	<5	<5	<10	169	5317	7	315	<10	34	142
196808	1361603	0.036	1	4.14	<2	77	<2	8	6.30	10	46	71	77	10.18	0.08	106	2.64	1530	<1	58	1015	9	0.65	<5	<5	<10	177	5796	8	333	<10	35	161
196809D	1361603	0.016	1	4.12	5	79	<2	7	6.39	10	47	73	75	10.33	0.09	108	2.73	1562	<1	61	1050	8	0.66	7	<5	<10	174	5505	5	338	<10	36	170
196810	1361604	0.015	1	6.47	3	111	<2	18	6.46	9	53	75	59	10.04	<0.01	113	2.51	2349	<1	80	1149	12	0.71	<5	<5	<10	193	7538	6	312	<10	45	159
196811	1361605	0.009	1	4.74	3	74	2	10	3.80	8	31	24	40	8.42	<0.01	125	1.93	1864	<1	39	1069	4	0.60	<5	<5	<10	133	5559	<2	196	<10	54	115
196812	1361606	0.017	1	5.79	6	119	3	6	3.99	8	34	29	40	9.02	<0.01	141	2.09	2037	<1	44	1222	10	0.64	9	<5	<10	146	6263	<2	212	<10	60	124
196813	1361607	0.015	1	5.52	<2	146	2	10	4.85	8	49	41	72	8.75	<0.01	150	2.00	1777	<1	58	1140	3	0.73	<5	<5	<10	177	7979	<2	277	<10	55	137
196814	1361608	<0.005	1	5.95	2	151	2	3	5.54	8	41	46	112	8.71	<0.01	113	1.93	2319	<1	60	948	14	0.81	<5	<5	<10	192	6552	4	251	<10	41	164
196815	1361609	0.019	1	5.22	12	75	2	16	5.68	10	50	63	204	10.04	<0.01	96	2.44	2238	<1	69	993	11	0.95	<5	<5	<10	178	7100	6	318	<10	41	137
196816	1361610	0.006	2	4.98	6	39	4	5	4.88	8	45	70	57	8.16	<0.01	81	2.25	2253	<1	71	1063	11	0.59	<5	<5	<10	177	6008	<2	274	<10	36	227
196817	1361611	0.005	1	4.37	<2	44	5	6	5.61	8	47	61	107	8.70	<0.01	70	2.22	2135	<1	66	1045	12	0.71	<5	<5	<10	214	6153	6	273	<10	36	171
196818	1361612	0.020	1	3.63	<2	75	<2	5	5.59	9	50	92	107	9.54	0.07	79	2.33	1836	4	132	992	15	0.78	7	<5	<10	176	6180	<2	314	<10	37	189

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/04/2012
 Date Completed:
 Job #: 201242633
 Reference: TL 12 251
 Sample #: 222

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
196819	1361613	0.011	1	3.58	<2	63	<2	14	5.70	10	52	78	103	10.27	0.10	77	2.56	2154	<1	91	1055	11	0.79	<5	<5	<10	179	6067	10	348	<10	38	255
196820D	1361613	0.037	1	3.58	<2	60	<2	7	5.70	10	53	86	104	10.35	0.09	76	2.60	2156	3	102	1061	9	0.77	<5	<5	<10	174	5806	<2	346	<10	40	256
196821	1361614	<0.005	1	4.00	4	463	<2	<1	2.74	<4	9	57	11	2.60	<0.01	109	1.43	789	7	104	444	6	0.70	<5	<5	<10	134	1840	<2	53	<10	9	41
196822	1361615	<0.005	1	5.05	4	418	6	3	2.76	<4	4	61	18	2.24	<0.01	110	1.33	718	10	117	533	10	0.64	9	<5	<10	146	1428	2	29	<10	7	50

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 21, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/20/2012
 Date Completed: 08/08/2012
 Job #: 201242756
 Reference: TL12252
 Sample #: 242

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
205437	1361616	0.025	2	6.66	9	568	<2	7	1.86	<4	6	51	28	1.98	0.19	22	0.72	588	11	64	294	7	1.18	6	<5	<10	156	1312	<2	37	10	7	30
205438	1361617	0.011	2	7.14	7	666	<2	12	1.75	<4	4	43	30	1.82	0.16	31	0.74	373	11	63	269	7	1.10	<5	<5	<10	185	1087	<2	20	<10	5	21
205439	1361618	0.005	2	7.43	5	775	<2	3	2.08	<4	5	46	3	1.56	0.24	34	0.56	236	12	61	272	10	1.23	<5	<5	<10	194	1067	5	20	<10	5	18
205440	1361619	<0.005	2	7.25	5	955	<2	<1	2.34	<4	5	42	2	1.46	0.37	26	0.62	218	9	52	273	1	1.03	5	<5	<10	191	1025	2	20	<10	5	22
205441	1361620	5.235	69	4.67	40	520	<2	<1	1.36	19	14	44	52	3.13	0.27	6	0.75	495	9	31	536	575	1.06	54	<5	241	233	2109	<2	91	68	13	1785
205442	1361621	<0.005	2	7.61	4	894	<2	11	2.51	<4	3	36	3	1.39	0.33	25	0.59	229	10	51	255	1	1.11	<5	<5	<10	228	1024	<2	20	10	5	20
205443	1361622	<0.005	2	7.41	3	822	<2	<1	2.14	<4	2	33	2	1.19	0.38	26	0.36	135	8	44	257	3	1.08	5	<5	<10	229	921	<2	18	<10	5	13
205444	1361623	<0.005	2	7.47	4	766	<2	3	2.50	<4	2	34	20	1.27	0.40	21	0.41	149	10	43	247	6	1.16	<5	<5	<10	244	860	<2	19	<10	5	19
205445	1361624	<0.005	2	6.65	<2	735	<2	16	2.06	<4	4	38	2	1.27	0.27	20	0.42	145	9	50	262	2	0.99	<5	<5	<10	229	819	<2	17	<10	5	19
205446	1361625	0.007	2	6.99	2	823	<2	17	1.93	<4	4	37	40	1.35	0.20	24	0.65	204	10	52	235	7	1.21	<5	<5	<10	228	953	<2	17	<10	5	48
205447D	1361625	0.008	2	6.39	<2	783	<2	6	1.82	<4	4	34	39	1.31	0.19	21	0.64	199	9	49	232	5	1.09	<5	<5	<10	221	906	5	16	<10	4	22
205448	1361626	0.009	2	7.32	5	839	<2	16	1.97	<4	4	39	40	1.29	0.05	24	0.62	196	11	53	240	3	1.14	<5	<5	<10	227	951	<2	17	<10	5	23
205449	1361627	0.018	3	7.73	6	866	<2	3	1.80	<4	4	37	57	1.45	0.15	28	0.85	354	11	47	252	6	1.32	<5	<5	<10	196	1009	3	18	<10	6	34
205450	1361628	0.016	2	7.51	5	880	<2	2	2.43	<4	3	48	10	1.45	0.23	26	0.66	329	12	65	238	8	1.34	<5	<5	<10	199	1010	<2	20	<10	5	30
205451	1361629	0.009	2	7.37	7	842	<2	4	2.65	<4	4	51	17	1.23	0.33	27	0.46	250	12	71	233	5	1.08	<5	<5	<10	230	982	<2	19	<10	5	43
205452	1361630	0.006	3	7.17	13	854	<2	5	2.57	<4	4	52	9	1.29	0.33	24	0.49	236	14	75	250	5	1.20	<5	<5	<10	206	953	<2	19	<10	5	25
205453	1361631	0.008	2	7.07	<2	1029	<2	6	1.20	<4	4	40	3	1.42	0.27	22	0.62	256	10	53	270	<1	1.42	<5	<5	<10	138	990	<2	20	<10	5	21
205454	1361632	0.009	2	6.96	5	1030	<2	9	1.23	<4	3	39	15	1.23	0.28	17	0.65	250	10	48	242	5	1.21	<5	<5	<10	139	937	3	17	11	4	59
205455	1361633	0.010	2	6.50	3	895	<2	3	2.84	<4	4	36	28	1.75	0.20	23	1.39	715	11	53	221	8	1.27	<5	<5	<10	152	883	<2	18	<10	5	97
205456	1361634	0.007	2	6.15	5	1119	<2	5	1.89	<4	3	37	6	1.46	0.30	26	1.05	404	9	52	244	10	1.25	<5	<5	<10	148	869	<2	18	<10	4	46

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 21, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/20/2012
 Date Completed: 08/08/2012
 Job #: 201242756
 Reference: TL12252
 Sample #: 242

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
205457	1361635	<0.005	2	5.95	<2	1187	<2	3	1.44	<4	4	41	3	1.30	0.25	30	0.75	251	10	48	261	10	1.27	<5	<5	<10	164	853	<2	18	<10	4	56
205458D	1361635	<0.005	2	6.06	<2	1220	<2	4	1.50	<4	4	43	4	1.33	0.17	31	0.76	256	9	52	266	8	1.34	<5	<5	<10	170	882	3	19	<10	4	94
205459	1361636	0.011	<1	6.71	2	1269	<2	11	1.44	<4	8	34	58	2.03	0.22	35	0.90	265	6	50	261	10	2.02	<5	<5	<10	185	814	3	17	<10	5	279
205460	1361637	<0.005	<1	8.33	5	1375	<2	8	1.88	<4	4	29	18	1.47	0.16	40	1.03	381	5	49	271	12	1.47	<5	<5	<10	200	927	<2	18	<10	6	35
205461	1361638	0.013	1	8.15	7	1389	<2	2	3.26	4	32	63	11	7.63	0.19	88	2.39	1114	5	84	1052	12	1.95	<5	<5	<10	107	5856	8	222	<10	15	89
205462	1361639	0.008	1	7.52	<2	1245	<2	8	2.81	<4	45	93	57	5.45	0.23	86	2.19	1207	6	103	1033	8	1.16	<5	<5	<10	127	6612	<2	217	<10	14	71
205463	1361640	<0.005	<1	6.20	2	433	2	8	2.59	<4	16	54	25	3.46	0.19	15	1.47	701	<1	36	613	8	0.67	<5	<5	<10	323	3039	<2	119	30	17	57
205464	1361641	0.006	<1	8.60	<2	1042	2	9	2.04	<4	3	36	10	1.17	0.19	51	1.22	520	6	55	295	9	0.91	5	<5	<10	162	1066	<2	18	10	7	82
205465	1361642	0.024	<1	7.43	3	879	<2	13	1.56	<4	3	38	15	0.99	0.22	42	0.95	392	6	60	282	8	0.75	<5	6	<10	161	945	<2	17	<10	6	42
205466	1361643	0.011	<1	8.25	10	735	2	12	1.58	<4	3	20	43	0.84	0.30	39	0.89	338	4	34	284	10	0.94	<5	<5	<10	201	928	4	16	<10	6	36
205467	1361644	0.011	<1	8.08	9	765	2	5	1.22	<4	5	24	9	1.04	0.26	33	0.69	273	4	46	291	7	1.06	<5	<5	<10	188	976	<2	18	<10	6	32
205468	1361645	0.015	1	8.10	<2	755	<2	10	3.09	<4	7	28	12	1.59	0.28	37	0.94	558	3	41	373	12	0.97	<5	<5	<10	187	1506	<2	32	<10	7	74
205469D	1361645	0.010	<1	7.50	5	730	<2	7	2.98	<4	7	27	12	1.56	0.36	34	0.92	548	4	41	369	11	0.93	<5	<5	<10	178	1444	3	30	<10	6	78
205470	1361646	0.010	<1	6.47	4	684	<2	14	2.76	<4	7	34	13	1.56	0.30	29	0.88	516	5	54	344	9	0.80	<5	<5	<10	159	1245	<2	28	<10	6	63
205471	1361647	0.007	<1	8.41	7	805	<2	7	2.89	<4	6	35	8	1.85	0.19	41	1.18	780	5	53	369	20	1.03	<5	<5	<10	187	1527	<2	37	<10	7	69
205472	1361648	0.014	3	6.91	<2	571	<2	11	4.51	7	21	55	42	5.79	0.16	58	2.90	1811	8	59	646	35	1.74	<5	<5	<10	156	3478	11	67	22	13	1279
205473	1361649	0.021	2	8.00	<2	428	2	16	6.67	6	37	54	58	7.96	0.18	50	2.49	2477	4	60	813	30	1.95	<5	<5	<10	160	5875	8	236	15	30	403
205474	1361650	0.020	2	6.42	<2	159	2	14	6.40	6	54	72	98	10.09	0.26	28	2.34	1884	3	87	979	14	1.25	<5	<5	<10	119	6408	9	340	31	39	171
205475	1361651	0.071	1	7.76	<2	155	<2	7	6.39	6	53	66	88	9.64	0.25	30	2.21	2045	2	71	984	14	1.28	<5	<5	<10	125	7550	<2	358	12	42	126
205476	1361652	0.044	2	5.48	5	241	2	6	5.28	5	27	69	80	7.59	0.23	30	2.38	1998	5	81	908	23	3.25	<5	<5	<10	152	3767	4	151	<10	18	186

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 21, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/20/2012
 Date Completed: 08/08/2012
 Job #: 201242756
 Reference: TL12252
 Sample #: 242

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
205477	1361653	0.016	1	8.16	<2	458	2	8	6.74	5	35	42	58	7.03	0.25	45	3.25	2177	3	57	881	26	1.74	<5	<5	<10	196	4973	28	219	37	21	208
205478	1361654	0.510	2	6.44	<2	372	2	17	5.65	5	50	62	101	8.99	0.28	37	3.01	1876	2	71	961	26	1.57	6	<5	<10	143	5970	29	326	10	34	211
205479	1361655	0.236	1	7.05	<2	318	2	20	5.94	6	51	69	86	9.94	0.34	37	2.46	2148	2	78	1008	13	1.02	5	<5	<10	169	6581	5	355	11	41	190
205480D	1361655	0.120	2	6.98	<2	315	2	16	5.90	6	52	74	85	10.00	0.34	36	2.45	2201	3	86	999	19	1.00	<5	<5	<10	168	6729	5	357	<10	41	187
205481	1361656	0.011	<1	5.83	<2	237	2	15	6.44	6	47	64	94	10.52	0.34	25	2.60	2227	2	73	909	18	1.02	<5	<5	<10	158	5466	12	326	<10	37	242
205482	1361657	0.607	<1	5.72	<2	209	<2	11	6.22	6	48	60	114	9.79	0.33	26	2.33	1950	1	69	959	20	1.01	<5	<5	<10	178	5372	11	318	14	37	153
205483	1361658	0.176	1	7.44	<2	241	2	6	6.92	6	54	69	104	10.82	0.25	35	2.69	2443	2	70	961	12	1.06	5	<5	<10	199	8071	5	358	13	41	176
205484	1361659	0.074	1	7.08	<2	220	2	9	6.60	6	52	65	61	10.75	0.25	32	2.66	2614	2	70	950	17	0.96	<5	<5	<10	204	7342	13	354	11	40	154
205485	1361660	1.981	1	6.28	11	455	<2	12	2.48	<4	18	54	33	3.72	0.28	16	1.50	729	2	38	633	10	0.69	<5	<5	<10	312	3044	6	122	29	17	60
205486	1361661	0.056	1	5.62	<2	177	<2	7	6.05	7	50	58	104	11.92	0.21	29	2.76	3635	1	67	898	23	1.39	8	<5	<10	171	5441	6	309	<10	35	180
205487	1361662	0.011	1	7.31	<2	380	2	8	6.06	6	60	65	107	9.37	0.24	45	2.54	1996	2	74	1039	20	1.13	<5	<5	<10	205	8194	13	377	11	42	170
205488	1361663	0.008	<1	5.92	11	325	<2	11	5.74	5	54	73	122	7.30	0.33	41	2.58	1605	2	88	901	24	0.84	5	<5	<10	214	5079	7	324	13	30	248
205489	1361664	0.021	1	3.75	<2	114	2	16	4.90	7	46	56	141	11.87	0.36	25	2.17	2860	2	70	822	15	1.44	5	<5	<10	148	3964	15	272	<10	30	237
205490	1361665	0.009	1	6.95	<2	125	2	21	5.77	6	53	67	108	10.82	0.27	32	2.33	2812	1	70	994	16	0.95	<5	<5	<10	253	6579	4	374	<10	42	168
205491D	1361665	0.007	<1	3.75	<2	91	<2	17	4.92	6	43	62	110	9.46	0.20	21	2.05	2277	<1	73	991	17	0.58	<5	<5	<10	184	3687	2	324	<10	37	154
205492	1361666	0.008	1	5.53	<2	122	2	7	5.47	6	52	66	102	10.31	0.35	27	2.22	2498	<1	72	989	17	0.78	<5	<5	<10	219	5473	<2	347	<10	40	152
205493	1361667	0.009	1	5.93	<2	316	2	2	5.65	7	50	61	86	10.53	0.37	38	2.68	2391	<1	65	957	22	0.88	<5	<5	<10	213	5864	2	360	10	40	271
205494	1361668	0.042	<1	6.14	<2	290	2	19	5.11	6	52	54	107	10.24	0.41	53	2.82	2112	2	71	846	21	1.20	<5	<5	<10	225	4511	21	309	10	35	219
205495	1361669	0.012	6	<0.01	<2	27	32	359	0.73	19	<1	30	70	2.20	<0.01	69	0.60	434	3	125	541	248	0.27	40	785	10	234	635	8	72	369	4	395
205496	1361670	0.014	1	5.83	<2	266	<2	15	5.59	6	54	60	88	9.91	0.34	48	2.89	1943	<1	67	956	7	1.10	<5	<5	<10	216	5128	20	342	<10	39	164

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 21, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/20/2012
 Date Completed: 08/08/2012
 Job #: 201242756
 Reference: TL12252
 Sample #: 242

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
205497	1361671	0.010	1	4.90	<2	114	<2	13	4.92	6	47	58	96	9.83	0.34	37	2.66	1803	<1	64	958	17	0.83	<5	<5	<10	215	4242	<2	330	10	38	166
205498	1361672	0.012	1	4.60	<2	165	<2	10	4.84	6	47	61	94	9.61	0.35	35	2.53	1659	<1	67	964	18	0.82	5	<5	<10	204	4220	<2	333	<10	37	202
205499	1361673	0.011	1	6.27	<2	81	2	12	5.79	6	48	58	94	10.43	0.35	37	2.84	1806	<1	60	923	14	0.94	<5	<5	<10	256	5268	<2	343	12	40	156
205500	1361674	0.015	1	6.18	<2	188	2	17	6.30	6	57	64	125	10.54	0.25	48	3.07	1726	<1	79	881	13	1.05	<5	<5	<10	287	5836	6	354	<10	38	156
205501	1361675	0.012	<1	5.54	<2	157	2	13	5.47	6	50	68	97	10.05	0.28	33	2.63	1592	4	80	928	6	0.95	<5	<5	<10	266	5572	36	339	<10	38	157
205502R	1361675	0.013	1	7.14	<2	169	2	4	5.94	6	51	64	101	10.65	0.33	40	2.82	1674	1	67	963	10	1.11	<5	<5	<10	297	6277	16	365	<10	41	161
205503	1361676	0.011	<1	5.44	<2	86	<2	8	5.10	6	48	59	103	10.21	0.42	30	2.82	1407	<1	63	1016	13	0.84	<5	<5	<10	232	4838	6	345	10	40	153
205504	1361677	0.009	1	7.06	<2	219	<2	7	4.52	5	42	56	78	8.25	0.40	47	2.23	1644	3	60	835	12	1.00	<5	<5	<10	211	5509	2	277	<10	32	137
205505	1361678	0.020	<1	5.44	<2	180	2	<1	5.32	6	52	65	103	9.14	0.42	27	2.51	1801	2	72	953	15	0.94	6	<5	<10	236	5409	32	335	<10	36	122
205506	1361679	0.013	1	7.22	<2	86	<2	21	5.69	6	52	63	130	10.06	0.32	24	2.64	1938	<1	74	888	22	1.21	<5	<5	<10	301	5875	28	365	13	37	129
205507	1361680	0.008	<1	5.80	2	400	<2	2	2.45	<4	16	51	23	3.32	0.27	15	1.44	668	<1	36	591	5	0.73	<5	<5	<10	301	2847	<2	114	25	17	56
205508	1361681	0.016	<1	6.86	3	70	<2	10	6.31	6	50	67	113	9.56	0.34	22	2.53	1949	3	74	903	18	1.17	6	<5	<10	301	6745	2	339	<10	36	145
205509	1361682	0.009	<1	6.78	<2	399	<2	<1	1.99	<4	6	25	6	1.27	0.33	18	0.55	283	4	40	370	9	0.73	<5	<5	<10	251	1431	<2	28	<10	6	38
205510	1361683	0.011	<1	7.33	<2	366	<2	6	2.07	<4	7	20	5	1.30	0.30	21	0.59	281	3	33	372	2	0.84	<5	<5	<10	254	1528	4	27	<10	6	43
205511	1361684	0.010	2	4.80	<2	388	<2	6	1.42	<4	5	30	8	1.21	0.22	15	0.56	278	7	41	349	8	0.64	<5	<5	<10	155	1166	<2	24	<10	4	36
205512	1361685	0.011	2	4.67	<2	369	<2	3	1.37	<4	7	39	12	1.29	0.25	15	0.54	298	9	45	371	2	0.58	<5	<5	<10	131	1325	<2	24	<10	4	29
205513D	1361685	0.011	2	7.20	12	430	<2	13	1.65	<4	5	43	12	1.33	0.22	20	0.54	304	11	47	381	4	0.84	<5	<5	<10	157	1469	<2	27	<10	6	31
205514	1361686	<0.005	<1	7.52	5	414	<2	10	1.72	<4	5	30	12	1.36	0.31	29	0.78	332	4	45	372	7	0.90	<5	<5	<10	183	1403	<2	26	<10	6	30
205515	1361687	0.017	<1	7.94	<2	452	<2	2	2.74	<4	6	23	14	1.52	0.29	33	1.07	495	3	33	381	8	0.95	5	<5	<10	204	1526	<2	26	<10	6	35
205516	1361688	0.011	<1	6.84	2	482	<2	7	1.86	<4	6	25	5	1.36	0.20	28	0.84	369	4	39	379	10	0.76	5	<5	<10	195	1471	<2	24	<10	6	43

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 21, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/20/2012
 Date Completed: 08/08/2012
 Job #: 201242756
 Reference: TL12252
 Sample #: 242

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
205517	1361689	0.005	<1	7.37	5	512	<2	4	2.01	<4	6	32	3	1.39	0.25	27	0.66	296	4	46	387	7	0.81	5	<5	<10	217	1446	5	27	<10	6	36
205518	1361690	0.011	<1	6.33	6	436	<2	5	1.82	<4	6	41	3	1.65	0.24	28	0.70	374	7	71	392	6	0.82	<5	<5	<10	210	1271	<2	30	<10	6	47
205519	1361691	0.007	<1	6.76	5	373	<2	6	2.16	<4	6	28	1	1.43	0.30	26	0.60	308	4	36	372	3	0.83	<5	<5	<10	217	1343	<2	26	<10	6	39
205520	1361692	0.009	<1	7.22	8	479	<2	<1	2.03	<4	4	39	2	1.52	0.20	34	0.79	369	7	68	376	5	0.86	<5	<5	<10	214	1226	4	27	<10	6	54
205521	1361693	0.006	<1	5.86	2	408	<2	12	1.76	<4	6	30	2	1.37	0.22	27	0.65	344	4	45	369	10	0.77	<5	<5	<10	170	1265	5	25	<10	5	34
205522	1361694	0.027	<1	7.47	<2	500	<2	9	1.94	<4	5	31	4	1.62	0.20	36	1.03	551	4	55	377	11	1.01	<5	<5	<10	190	1496	<2	26	<10	6	250
205523	1361695	<0.005	<1	5.98	2	447	<2	<1	1.85	<4	5	29	2	1.37	0.24	32	0.79	433	4	47	365	12	0.80	<5	<5	<10	146	1318	<2	24	<10	5	42
205524D	1361695	<0.005	<1	7.65	3	479	<2	5	2.08	<4	5	33	3	1.41	0.27	38	0.85	440	4	51	365	<1	0.98	<5	<5	<10	166	1434	<2	26	10	6	40
205525	1361696	0.037	1	7.46	4	355	2	13	4.01	5	32	66	57	7.67	0.34	50	1.48	1379	5	76	426	17	3.60	<5	<5	<10	188	2681	7	83	11	12	197
205526	1361697	0.013	1	7.17	<2	352	<2	3	4.38	4	40	68	76	6.58	0.28	63	1.65	1646	5	85	711	9	1.39	5	<5	<10	171	6159	2	203	10	24	253
205527	1361698	0.031	2	7.28	<2	281	2	17	4.11	5	39	99	108	8.58	0.30	81	2.31	1825	4	83	658	17	2.76	<5	<5	<10	182	5045	6	188	16	20	352
205528	1361699	0.025	1	7.26	10	435	<2	10	3.00	<4	11	56	21	3.09	0.23	50	1.51	1098	7	72	394	20	1.46	<5	<5	<10	150	1887	<2	47	13	8	88
205529	1361700	0.242	1	0.65	409	>5000	<2	6	0.93	<4	4	18	31	2.83	0.21	6	0.23	<100	13	19	<100	18	1.06	13	<5	<10	125	726	<2	15	55	8	22
205530	1361701	0.020	<1	7.35	3	438	2	5	2.06	<4	8	32	11	1.75	0.33	56	1.04	530	4	49	402	13	1.13	<5	<5	<10	144	1593	<2	29	11	6	145
205531	1361702	0.008	<1	5.30	6	420	<2	<1	2.03	<4	6	37	10	1.50	0.23	44	0.74	418	5	58	425	11	0.65	5	<5	<10	136	1454	2	27	<10	6	47
205532	1361703	<0.005	<1	6.25	3	412	<2	<1	2.29	<4	8	42	6	1.73	0.35	55	1.07	529	4	69	490	12	0.77	<5	<5	<10	150	1614	3	32	<10	6	54
205533	1361704	0.011	<1	7.24	7	404	<2	3	2.94	<4	16	62	24	3.49	0.28	78	1.42	1004	5	68	488	20	1.25	<5	<5	<10	178	2747	<2	79	<10	10	91
205534	1361705	0.011	<1	6.18	<2	217	3	14	3.19	<4	24	90	44	5.33	0.38	71	1.79	1507	3	71	552	14	1.11	<5	<5	<10	148	3498	3	130	<10	13	105
205535D	1361705	0.012	<1	4.01	<2	183	2	<1	2.63	<4	21	78	39	4.72	0.51	58	1.57	1336	2	64	485	8	0.89	<5	<5	<10	119	2976	<2	114	<10	11	96
205536	1361706	0.012	<1	6.93	2	225	4	11	2.90	<4	22	81	38	4.59	0.40	73	1.64	1362	2	56	572	12	1.01	<5	<5	<10	152	3303	<2	121	<10	12	101

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 21, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/20/2012
 Date Completed: 08/08/2012
 Job #: 201242756
 Reference: TL12252
 Sample #: 242

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
205537	1361707	0.011	<1	6.33	<2	255	<2	6	4.09	<4	33	104	44	5.26	0.34	88	2.22	1641	1	76	620	6	0.88	<5	<5	<10	180	4348	4	162	<10	14	116
205538	1361708	0.018	<1	6.43	<2	236	<2	15	4.78	4	31	98	78	6.17	0.30	75	2.18	1607	2	75	611	6	1.19	5	<5	<10	201	4176	<2	159	<10	15	122
205539	1361709	0.021	1	6.70	<2	217	2	4	4.62	4	29	95	53	7.11	0.32	77	1.99	1703	3	69	561	2	1.61	<5	5	<10	183	3572	<2	150	<10	14	186
205540	1361710	0.015	<1	7.16	<2	281	<2	8	4.83	5	36	99	70	7.87	0.32	94	2.23	1721	3	74	575	1	1.61	<5	<5	<10	178	4045	5	158	<10	15	131
205541	1361711	0.011	<1	8.22	3	360	<2	14	5.19	<4	32	106	39	5.05	0.28	89	2.05	1578	3	71	593	5	1.08	<5	<5	<10	244	4316	<2	155	<10	15	114
205542	1361712	0.016	1	6.92	<2	247	3	11	4.06	4	31	88	92	7.05	0.36	86	1.87	1699	2	59	507	10	1.89	<5	<5	<10	174	3383	<2	134	11	13	143
205543	1361713	0.011	<1	7.50	<2	216	<2	15	5.85	<4	25	80	42	5.38	0.21	79	1.81	1647	2	56	560	8	1.36	5	<5	<10	188	3575	<2	126	<10	17	126
205544	1361714	0.013	1	6.43	<2	205	<2	24	3.76	5	28	82	56	8.18	0.39	114	2.16	1863	1	63	612	11	1.76	<5	<5	<10	156	3187	5	135	<10	17	268
205545	1361715	0.013	1	8.77	<2	224	<2	9	4.42	4	27	89	49	7.13	0.35	124	2.19	1659	2	62	662	4	1.66	<5	<5	<10	208	4264	<2	149	<10	18	201
205546D	1361715	0.014	<1	5.78	<2	184	<2	9	3.54	4	23	74	43	6.24	0.45	103	1.90	1397	1	56	587	7	1.26	6	<5	<10	163	3177	<2	125	10	15	179
205547	1361716	0.017	<1	7.34	<2	201	<2	15	4.91	5	34	83	64	7.50	0.29	88	2.14	1802	2	68	664	13	2.11	<5	<5	<10	215	4424	5	140	10	17	191
205548	1361717	0.030	1	>10.00	6	200	3	22	5.07	5	24	82	73	7.79	0.32	101	2.13	2089	2	69	614	17	2.38	<5	<5	<10	240	4368	<2	132	<10	20	273
205549	1361718	0.027	2	8.17	<2	152	4	9	4.90	8	45	103	103	11.52	0.31	87	2.01	2772	5	100	812	23	4.02	<5	<5	<10	231	4535	<2	112	14	18	536
205550	1361719	0.196	1	5.50	<2	104	3	19	5.69	7	30	109	33	11.81	0.23	55	2.46	3420	1	74	1048	10	1.62	<5	<5	<10	198	4514	13	122	15	20	126
205551	1361720	0.009	<1	6.70	4	436	<2	5	2.60	<4	16	53	23	3.40	0.21	16	1.48	685	<1	35	607	5	0.78	<5	<5	<10	318	2984	6	117	27	17	52
205552	1361721	0.359	1	8.05	<2	310	2	26	5.39	5	41	83	48	8.60	0.26	40	1.80	2027	<1	98	758	11	2.59	5	<5	<10	293	4375	<2	122	11	17	89
205553	1361722	0.016	1	6.38	<2	334	2	9	5.10	5	67	191	66	8.78	0.15	55	1.96	2085	3	160	889	15	1.76	<5	<5	<10	246	5568	7	155	14	20	169
205554	1361723	0.049	1	8.75	6	353	2	6	5.70	5	60	358	61	8.85	0.22	60	2.12	2536	4	177	1033	8	1.83	<5	<5	<10	213	7386	7	185	12	25	164
205555	1361724	0.014	<1	5.55	<2	191	<2	10	3.35	4	50	338	52	7.49	0.16	58	1.81	1764	7	182	1047	9	1.00	5	<5	<10	145	5580	<2	179	11	22	136
205556	1361725	0.039	<1	8.45	<2	346	5	17	5.25	<4	50	297	47	6.04	0.16	70	1.67	1201	1	147	1380	4	0.95	<5	<5	<10	270	9083	3	200	<10	27	107

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 21, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/20/2012
 Date Completed: 08/08/2012
 Job #: 201242756
 Reference: TL12252
 Sample #: 242

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
205557D	1361725	0.045	<1	8.87	4	347	5	7	5.25	4	52	296	46	6.11	0.31	72	1.65	1317	1	141	1378	1	0.99	<5	<5	<10	272	10374	2	202	<10	26	102
205558	1361726	0.020	<1	8.35	3	331	5	13	5.24	4	47	287	47	5.92	0.26	68	1.65	1172	2	145	1345	6	0.92	7	<5	<10	265	8466	<2	197	<10	26	91
205559	1361727	0.014	<1	7.43	<2	234	2	7	5.83	<4	50	219	39	5.82	0.29	64	1.70	1085	2	128	1392	8	0.74	<5	<5	<10	334	10432	12	209	<10	27	122
205560	1361728	<0.005	1	8.42	<2	119	<2	17	6.49	4	53	216	63	6.65	0.32	37	2.29	1276	<1	143	1302	2	0.90	<5	<5	<10	349	9848	<2	207	<10	28	111
205561	1361729	<0.005	<1	7.92	3	155	2	17	5.88	<4	46	191	54	6.01	0.30	29	2.11	1344	3	117	1399	9	0.78	5	<5	<10	338	10933	<2	208	<10	28	96
205562	1361730	0.005	<1	9.01	3	170	2	15	5.70	4	53	286	65	6.93	0.23	58	2.48	1309	2	156	1438	8	0.93	<5	<5	<10	379	8119	7	223	11	30	126
205563	1361731	0.013	<1	8.03	<2	230	<2	4	3.69	4	42	585	75	7.11	0.21	72	1.92	1522	4	160	1245	12	1.50	<5	<5	<10	313	4862	<2	167	<10	19	212
205564	1361732	0.039	<1	7.66	3	208	<2	14	5.93	5	50	257	94	7.69	0.22	51	1.85	1711	4	186	1193	13	1.50	6	<5	<10	315	6331	<2	195	<10	26	317
205565	1361733	0.010	1	8.30	5	296	<2	15	5.44	4	51	274	62	7.01	0.31	55	1.87	1672	3	182	1349	11	1.14	<5	<5	<10	287	7748	6	176	10	25	164
205566	1361734	0.008	1	8.76	<2	307	2	10	6.49	4	67	463	53	6.63	0.28	54	2.68	1349	2	285	1710	8	0.87	<5	<5	<10	342	11630	17	207	10	26	134
205567	1361735	0.006	<1	7.45	<2	162	2	15	6.00	5	50	315	43	7.78	0.22	49	4.03	1044	<1	201	1581	5	0.78	5	<5	<10	326	7310	7	186	<10	25	116
205568R	1361735	0.011	<1	7.84	<2	161	2	15	6.17	4	52	330	41	7.92	0.26	50	4.15	1056	<1	205	1592	2	0.79	6	<5	<10	332	7325	31	187	10	25	117
205569	1361736	0.034	<1	6.99	<2	158	2	11	5.47	5	43	253	48	7.42	0.29	42	3.76	852	<1	155	1669	6	0.73	<5	<5	<10	334	5604	15	189	<10	25	109
205570	1361737	<0.005	<1	7.47	<2	254	<2	16	6.55	4	51	276	48	7.33	0.26	42	2.89	1023	1	174	1655	8	0.80	<5	<5	<10	363	7421	16	195	<10	25	123
205571	1361738	0.005	<1	7.53	<2	238	<2	8	4.65	<4	41	234	48	5.29	0.30	38	1.57	1313	1	133	1633	3	0.77	5	<5	<10	375	5996	8	173	<10	22	88
205572	1361739	0.015	1	7.75	<2	177	<2	5	5.69	5	35	88	37	8.50	0.35	39	2.17	2613	2	91	1857	5	0.97	<5	<5	<10	297	6043	<2	140	<10	21	130
205573	1361740	4.897	70	4.75	39	495	<2	10	1.49	20	15	36	55	3.12	0.21	12	0.95	521	4	33	559	607	0.95	52	<5	254	262	2025	7	91	65	14	1891
205574	1361741	0.010	1	8.01	<2	214	2	13	4.85	4	34	100	9	7.39	0.30	42	1.91	2290	2	98	2319	4	0.81	<5	<5	<10	285	5696	<2	155	10	20	82
205575	1361742	0.207	1	7.55	<2	200	2	16	5.61	4	39	106	38	7.87	0.39	35	2.23	2198	1	109	2323	4	0.70	7	<5	<10	256	5442	<2	156	<10	21	100
205576	1361743	0.009	<1	7.68	<2	273	<2	15	5.62	4	40	111	56	5.89	0.41	42	2.41	1403	<1	121	2428	8	0.79	5	<5	<10	282	5626	9	157	10	21	110

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 21, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/20/2012
 Date Completed: 08/08/2012
 Job #: 201242756
 Reference: TL12252
 Sample #: 242

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
205577	1361744	<0.005	1	8.14	5	318	<2	7	4.89	<4	42	123	51	5.35	0.41	45	2.28	1105	2	128	2521	7	0.74	<5	<5	<10	243	6262	<2	166	<10	21	107
205578	1361745	0.219	<1	8.31	<2	347	<2	5	6.19	4	41	106	45	6.08	0.32	46	2.57	1561	3	123	2363	5	0.83	7	<5	<10	264	6771	4	159	<10	21	114
205579D	1361745	0.273	1	9.41	2	353	<2	8	6.27	4	43	105	44	6.19	0.28	49	2.60	1678	3	118	2323	6	0.95	<5	<5	<10	276	8319	9	164	10	22	112
205580	1361746	0.006	1	8.34	<2	340	<2	7	6.35	4	41	103	49	6.16	0.27	46	2.61	1635	2	113	2193	3	0.85	<5	<5	<10	262	6817	<2	157	10	21	111
205581	1361747	0.009	1	8.25	<2	348	<2	5	3.97	4	35	117	55	6.10	0.29	51	2.18	1248	3	98	1823	15	0.92	<5	<5	<10	239	6073	17	167	<10	20	121
205582	1361748	0.008	1	9.42	<2	269	<2	18	5.64	4	39	138	80	7.39	0.44	52	2.66	1853	4	114	1146	6	1.25	5	<5	<10	247	6955	6	152	10	21	139
205583	1361749	0.044	1	7.92	<2	308	<2	3	5.29	<4	31	121	46	5.83	0.41	49	2.53	1412	3	104	973	11	0.79	6	<5	<10	182	4853	3	133	<10	16	111
205584	1361750	0.029	1	7.40	<2	309	<2	11	3.85	<4	25	129	35	5.63	0.34	51	2.37	1622	2	96	754	5	1.22	<5	<5	<10	167	3894	<2	105	11	15	106
205585	1361751	0.015	2	6.53	<2	260	<2	6	9.13	4	26	90	55	6.51	0.54	44	3.95	2723	2	111	479	9	1.51	<5	<5	<10	221	3128	9	94	10	15	175
205586	1361752	<0.005	1	8.76	<2	363	<2	10	5.56	5	56	79	107	9.24	0.57	60	2.41	2136	2	70	1029	8	1.26	<5	<5	<10	260	9331	4	380	<10	42	119
205587	1361753	<0.005	1	7.77	<2	114	2	16	6.78	6	53	72	103	11.05	0.51	33	2.92	1654	2	70	1000	9	1.07	<5	<5	<10	262	7233	7	381	11	44	139
205588	1361754	<0.005	1	7.01	<2	111	2	13	5.87	6	53	66	110	11.33	0.38	33	3.25	1743	2	66	1016	8	1.24	8	<5	<10	238	6827	<2	380	10	43	156
205589	1361755	0.006	1	6.67	<2	232	<2	21	6.19	6	52	74	123	10.77	0.32	34	2.94	1690	2	71	1027	7	1.11	<5	<5	<10	275	6590	18	352	15	42	130
205590D	1361755	0.011	1	6.19	<2	225	2	7	5.92	6	52	71	121	10.34	0.38	32	2.83	1620	1	71	1002	12	1.06	<5	<5	<10	257	6111	16	335	<10	41	124
205591	1361756	<0.005	<1	6.21	<2	161	2	6	5.79	6	48	73	101	10.06	0.40	32	2.94	1539	2	77	994	11	0.89	<5	<5	<10	237	5453	13	309	<10	39	118
205592	1361757	0.007	<1	4.53	<2	204	<2	5	5.06	6	48	44	122	10.45	0.31	31	2.87	1577	1	59	1101	7	1.04	<5	<5	<10	210	4548	8	337	<10	41	134
205593	1361758	<0.005	1	6.58	<2	199	2	18	6.20	6	50	65	102	10.94	0.30	35	3.12	1761	1	68	1021	8	1.01	6	<5	<10	251	6224	8	354	13	42	149
205594	1361759	<0.005	<1	6.07	<2	44	2	22	5.21	7	52	60	135	11.33	0.29	41	2.95	1455	2	69	1053	8	1.02	<5	<5	<10	214	6595	19	388	<10	43	126
205595	1361760	<0.005	<1	5.72	<2	430	<2	3	2.54	<4	17	54	23	3.45	0.37	13	1.48	694	<1	37	611	8	0.64	<5	<5	<10	306	2911	2	118	26	17	53
205596	1361761	<0.005	1	6.19	<2	23	2	17	5.40	6	47	63	112	11.06	0.45	41	2.99	1441	2	69	1051	6	0.99	<5	<5	<10	331	5297	9	375	24	43	130

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 21, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/20/2012
 Date Completed: 08/08/2012
 Job #: 201242756
 Reference: TL12252
 Sample #: 242

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
205597	1361762	<0.005	<1	6.16	<2	16	2	23	5.72	6	51	74	101	11.00	0.47	36	2.96	1456	3	78	1053	8	0.87	<5	<5	<10	345	5554	<2	370	<10	43	121
205598	1361763	0.005	1	7.02	<2	19	2	16	6.22	6	51	78	95	10.90	0.48	34	2.90	1493	3	72	989	12	0.95	<5	<5	<10	360	6209	4	358	11	43	121
205599	1361764	<0.005	<1	5.99	<2	27	2	20	5.88	6	51	76	106	10.89	0.46	29	2.98	1474	1	72	1000	6	0.85	<5	<5	<10	228	5330	9	356	<10	42	123
205600	1361765	<0.005	<1	5.14	<2	52	<2	19	6.80	6	47	68	105	10.72	0.46	30	3.21	1710	1	61	1152	11	0.81	<5	<5	<10	234	4483	11	320	<10	42	113
205601D	1361765	0.011	<1	6.35	<2	62	2	13	7.07	6	48	71	107	11.04	0.31	35	3.31	1783	2	65	1198	12	0.95	5	<5	<10	253	5439	8	326	11	43	113
205602	1361766	0.007	<1	7.38	<2	75	2	23	7.13	7	58	78	105	11.70	0.24	38	3.43	1891	2	70	1081	7	1.08	<5	<5	<10	257	8023	4	352	<10	45	123
205603	1361767	<0.005	<1	5.18	<2	12	<2	13	5.23	6	50	80	100	10.64	0.27	35	3.11	1402	3	78	995	4	0.71	<5	<5	<10	213	4911	5	338	<10	41	111
205604	1361768	0.006	<1	5.54	<2	14	2	9	5.50	6	50	69	101	10.55	0.19	36	3.09	1408	<1	66	975	6	0.73	6	<5	<10	303	5791	3	343	<10	40	114
205605	1361769	<0.005	<1	4.22	<2	7	2	7	5.00	6	46	67	106	10.25	0.36	29	2.89	1383	<1	63	997	9	0.68	<5	<5	<10	260	3957	<2	337	<10	40	116
205606	1361770	<0.005	1	6.71	<2	33	4	17	5.88	7	54	72	92	10.89	0.34	35	3.15	1450	2	58	993	10	0.30	<5	<5	<10	324	7144	4	367	<10	43	111
205607	1361771	<0.005	<1	3.72	<2	189	2	14	4.89	5	47	69	107	9.74	0.37	32	2.75	1572	<1	64	989	7	0.64	<5	<5	<10	143	3701	7	332	<10	38	104
205608	1361772	<0.005	1	6.66	<2	276	<2	15	5.72	6	48	72	78	10.27	0.37	40	2.94	1522	<1	66	1021	8	0.88	5	<5	<10	220	6499	7	359	<10	41	122
205609	1361773	<0.005	<1	5.63	<2	5	2	11	5.30	7	46	69	115	10.45	0.39	36	3.13	1378	<1	64	992	15	0.75	<5	<5	<10	185	4386	3	349	12	41	111
205610	1361774	<0.005	<1	5.41	<2	8	2	22	5.17	6	47	71	103	10.64	0.29	37	2.99	1408	<1	64	983	7	0.78	<5	<5	<10	276	4733	8	359	<10	42	118
205611	1361775	<0.005	<1	5.44	<2	7	2	7	5.05	7	49	70	110	10.97	0.32	43	3.02	1429	2	65	1005	5	0.66	<5	<5	<10	336	4860	3	364	<10	42	117
205612D	1361775	<0.005	<1	4.91	<2	5	2	10	4.85	6	48	75	110	10.62	0.44	41	2.94	1381	<1	71	996	8	0.67	<5	<5	<10	301	4202	3	352	<10	41	113
205613	1361776	0.006	<1	5.75	<2	12	2	4	4.85	6	47	55	97	10.68	0.29	55	3.02	1393	<1	54	1039	<1	0.81	<5	<5	<10	234	5574	<2	369	<10	44	105
205614	1361777	0.009	1	8.68	<2	34	2	20	5.65	7	53	56	97	11.41	0.13	53	3.03	1485	3	61	1056	10	1.14	<5	<5	<10	321	7738	24	386	11	46	119
205615	1361778	0.005	1	7.27	<2	29	<2	8	5.78	7	51	66	98	10.78	0.16	40	3.04	1491	<1	57	990	11	1.00	<5	<5	<10	204	7031	8	359	<10	42	114
205616	1361779	0.006	1	7.40	<2	28	2	16	5.91	7	55	69	72	11.75	0.27	46	3.19	1623	<1	65	931	6	0.87	6	<5	<10	194	8145	5	405	<10	45	127

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 21, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/20/2012
 Date Completed: 08/08/2012
 Job #: 201242756
 Reference: TL12252
 Sample #: 242

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
205617	1361780	1.962	<1	6.97	11	480	<2	3	2.58	<4	19	62	33	3.85	0.27	18	1.55	742	1	40	627	6	0.79	6	<5	<10	316	3223	<2	125	27	17	62
205618	1361781	0.006	<1	5.86	2	18	2	11	5.43	6	48	58	118	10.69	0.31	37	2.98	1476	2	60	1024	1	0.89	5	<5	<10	225	5321	16	354	11	42	117
205619	1361782	0.006	<1	5.65	<2	24	2	10	5.59	6	48	66	92	10.81	0.47	50	3.03	1475	1	65	1012	2	0.78	<5	<5	<10	258	4429	2	353	<10	42	133
205620	1361783	0.006	1	7.13	<2	38	2	12	5.84	7	53	70	97	11.43	0.37	48	3.02	1534	2	67	1044	6	0.92	<5	<5	<10	408	7092	<2	385	<10	44	135
205621	1361784	0.007	1	6.74	2	53	<2	19	6.27	6	54	77	129	11.07	0.37	43	2.84	1574	2	74	1023	14	1.06	<5	<5	<10	219	6778	9	366	10	42	134
205622	1361785	0.009	1	7.50	<2	140	2	16	5.68	7	56	72	134	11.19	0.46	46	2.81	1543	2	71	1043	12	1.18	<5	<5	<10	276	6690	16	391	<10	45	128
205623D	1361785	0.008	1	7.97	<2	143	2	19	5.79	7	58	74	134	11.45	0.39	48	2.86	1599	3	74	1055	17	1.25	6	<5	<10	282	7772	<2	396	<10	45	129
205624	1361786	0.006	1	8.59	<2	132	2	6	5.99	6	56	69	119	11.04	0.42	46	2.78	1567	3	68	1051	10	1.33	<5	<5	<10	280	8068	6	378	11	45	122
205625	1361787	0.009	1	7.63	<2	56	2	14	5.74	6	50	67	125	10.91	0.50	49	3.00	1385	2	66	991	16	1.31	5	<5	<10	283	5804	6	363	11	43	119
205626	1361788	0.005	<1	6.35	<2	112	2	15	6.03	6	48	71	67	10.63	0.45	50	3.10	1448	2	65	978	6	0.84	<5	<5	<10	255	5220	8	347	10	41	120
205627	1361789	0.008	<1	6.78	<2	130	2	13	6.18	7	54	75	139	10.84	0.35	52	2.90	1485	2	69	986	11	1.01	<5	<5	<10	295	6012	<2	365	12	42	125
205628	1361790	0.008	1	7.23	<2	167	2	7	6.05	7	53	75	123	11.20	0.31	61	2.97	1520	2	69	1025	14	1.13	7	<5	<10	248	6115	9	380	<10	44	130
205629	1361791	0.007	<1	7.54	<2	131	3	11	4.76	5	43	58	87	9.02	0.13	67	2.41	1311	1	49	950	4	1.14	5	<5	<10	204	5694	5	311	12	37	110
205630	1361792	<0.005	<1	7.48	<2	47	5	7	3.66	5	33	53	51	7.03	0.46	81	2.04	1096	<1	44	737	3	1.00	<5	<5	<10	184	4877	2	232	<10	29	202
205631	1361793	0.006	<1	6.84	<2	61	5	21	4.84	6	46	61	62	10.45	0.49	135	2.97	1458	<1	56	938	6	0.86	5	<5	<10	189	5481	3	355	10	40	159
205632	1361794	0.006	<1	7.58	<2	21	2	12	5.30	6	52	67	107	11.48	0.42	85	3.26	1512	<1	58	999	17	0.94	<5	<5	<10	260	6455	16	391	<10	44	127
205633	1361795	<0.005	1	7.21	<2	20	2	16	5.04	6	52	68	94	11.53	0.34	87	3.30	1496	<1	56	1005	9	0.92	<5	<5	<10	263	7436	6	379	12	43	126
205634R	1361795	<0.005	<1	8.14	<2	25	2	19	5.12	7	52	66	91	11.61	0.39	91	3.35	1495	<1	54	1044	8	1.02	5	<5	<10	278	6639	9	382	<10	45	127
205635	1361796	<0.005	<1	7.62	<2	27	3	14	5.83	7	55	68	98	11.64	0.40	73	3.14	1556	1	58	1073	9	1.02	<5	<5	<10	258	7309	12	398	11	44	128
205636	1361797	0.007	<1	6.95	3	133	3	20	5.68	6	48	64	110	9.91	0.46	50	2.71	1416	<1	52	921	4	1.04	<5	<5	<10	231	6387	4	344	<10	39	105

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 21, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/20/2012
 Date Completed: 08/08/2012
 Job #: 201242756
 Reference: TL12252
 Sample #: 242

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
205637	1361798	0.005	<1	6.70	<2	127	<2	14	6.50	7	51	93	106	10.39	0.38	52	2.95	1456	<1	74	940	7	0.79	<5	<5	<10	346	5676	<2	329	<10	39	120
205638	1361799	0.018	1	7.47	<2	168	2	14	6.48	6	53	85	120	10.30	0.32	38	2.91	1480	1	84	842	10	0.88	<5	<5	<10	333	6348	17	329	<10	37	117
205639	1361800	<0.005	<1	6.90	6	458	<2	15	2.72	<4	17	56	25	3.56	0.35	16	1.55	722	1	36	654	7	0.80	8	<5	<10	332	3143	<2	123	28	18	59
205640	1361801	<0.005	1	7.88	<2	124	<2	19	6.29	6	54	60	91	10.31	0.37	43	2.89	1503	<1	79	860	3	1.01	<5	<5	<10	268	6562	<2	326	<10	38	123
205641	1361802	<0.005	<1	6.86	<2	113	2	16	6.15	6	59	67	107	10.08	0.34	38	2.55	1581	2	82	951	1	0.87	<5	<5	<10	224	7061	6	370	13	38	131
205642	1361803	<0.005	1	7.18	<2	76	2	13	6.12	6	53	64	98	10.16	0.35	33	2.38	1624	<1	65	1003	<1	0.90	6	<5	<10	222	6633	10	369	13	42	126
205643	1361804	0.011	<1	5.84	<2	29	2	6	6.53	6	49	61	94	10.43	0.36	37	2.65	1413	<1	64	973	11	0.80	<5	<5	<10	254	5481	23	341	11	40	119
205644	1361805	<0.005	<1	6.65	<2	107	<2	17	6.51	5	47	58	92	9.76	0.32	36	2.32	1539	2	61	854	10	0.83	6	<5	<10	275	7154	<2	316	<10	36	106
205645D	1361805	0.008	<1	6.61	<2	107	2	12	6.49	6	50	58	93	9.80	0.35	36	2.32	1555	1	63	861	8	0.83	<5	<5	<10	273	7574	4	316	<10	36	109
205646	1361806	<0.005	<1	5.98	<2	96	<2	17	6.51	6	48	63	90	9.90	0.29	33	2.34	1516	1	70	884	6	0.75	<5	<5	<10	252	6910	<2	320	<10	37	107
205647	1361807	0.008	<1	5.24	4	128	2	11	6.62	6	48	62	95	10.15	0.29	22	2.54	1571	<1	69	972	11	0.74	5	<5	<10	260	5840	<2	330	<10	41	109
205648	1361808	0.014	<1	4.33	<2	70	2	15	5.82	6	47	61	102	9.82	0.22	23	2.81	1341	<1	61	954	10	0.61	<5	<5	<10	210	4595	23	343	<10	39	109
205649	1361809	<0.005	<1	5.97	<2	210	2	9	5.65	6	51	66	118	9.69	0.42	30	2.57	1512	2	70	1003	9	0.81	<5	<5	<10	247	5421	20	350	<10	39	124
205650	1361810	0.010	<1	7.06	<2	72	<2	21	6.47	6	51	64	85	10.41	0.38	32	2.99	1520	<1	71	895	11	0.89	<5	<5	<10	318	5688	5	334	<10	38	124
205651	1361811	0.019	1	5.23	<2	326	<2	12	5.57	7	37	55	88	11.31	0.31	28	2.08	3149	1	63	859	18	1.37	5	<5	<10	186	3733	<2	294	135	35	167
205652	1361812	0.013	1	6.66	<2	118	2	11	5.82	6	53	56	104	11.10	0.31	37	2.56	1844	1	61	992	8	0.95	<5	<5	<10	241	6531	15	368	10	41	134
205653	1361813	0.006	<1	5.08	<2	6	2	11	6.89	6	50	56	92	10.79	0.28	36	2.88	1518	<1	59	935	17	0.73	6	<5	<10	308	5002	14	354	<10	39	122
205654	1361814	<0.005	<1	5.87	<2	11	<2	16	5.77	6	49	53	98	11.21	0.29	40	2.97	1465	<1	61	1000	9	0.76	6	<5	<10	362	4986	7	371	<10	42	129
205655	1361815	<0.005	<1	7.25	<2	16	2	12	5.87	6	51	55	105	10.68	0.33	38	2.71	1494	<1	61	1034	1	0.94	<5	<5	<10	289	5948	4	365	<10	42	115
205656D	1361815	<0.005	<1	6.10	<2	9	2	19	5.77	6	50	54	107	10.64	0.28	34	2.72	1476	<1	62	1042	8	0.80	<5	<5	<10	274	5023	6	363	<10	42	117

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 21, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/20/2012
 Date Completed: 08/08/2012
 Job #: 201242756
 Reference: TL12252
 Sample #: 242

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
205657	1361816	0.006	<1	6.64	<2	149	2	18	6.21	6	56	62	148	10.51	0.35	25	2.44	2143	<1	71	1039	9	1.02	<5	<5	<10	171	5807	3	389	10	40	141
205658	1361817	0.007	<1	7.15	<2	74	<2	18	6.18	6	47	70	115	9.33	0.23	25	2.80	1645	<1	63	947	8	0.85	<5	<5	<10	203	5093	6	331	<10	36	108
205659	1361818	<0.005	<1	6.56	<2	21	<2	20	6.66	6	49	74	106	9.99	0.41	25	3.20	1441	<1	68	908	12	0.79	7	<5	<10	247	4715	16	336	<10	35	110
205660	1361819	<0.005	<1	7.16	<2	19	<2	13	6.30	6	49	55	114	10.08	0.42	28	2.91	1500	<1	51	1031	<1	0.91	5	<5	<10	271	4964	7	376	<10	39	104
205661	1361820	0.231	1	1.32	436	>5000	<2	11	1.05	<4	7	18	33	3.00	0.35	8	0.27	<100	13	19	<100	21	1.11	11	<5	<10	137	836	<2	16	48	9	28
205662	1361821	<0.005	<1	6.93	<2	24	2	12	6.07	6	48	52	108	10.66	0.35	27	3.02	1436	<1	56	1082	16	0.89	<5	<5	<10	305	5091	4	382	<10	39	111
205663	1361822	0.028	<1	7.58	<2	32	<2	20	7.02	5	49	114	99	9.48	0.33	23	3.19	1388	1	76	823	10	0.88	5	<5	<10	288	6403	<2	326	<10	33	102
205664	1361823	<0.005	<1	7.21	<2	125	2	14	6.81	6	48	96	97	10.20	0.24	41	3.54	1987	2	70	861	10	1.05	5	<5	<10	183	5097	3	335	223	35	130
205665	1361824	0.014	<1	5.83	<2	15	2	9	5.66	6	47	36	100	10.73	0.22	35	3.17	1496	<1	51	1062	10	0.78	<5	<5	<10	276	4568	<2	385	<10	39	110
205666	1361825	0.192	<1	5.67	<2	4	<2	16	5.90	6	47	89	144	10.14	0.25	29	3.28	1473	2	76	865	8	0.73	6	<5	<10	302	4490	<2	349	<10	34	110
205667D	1361825	0.014	<1	7.09	<2	13	2	8	6.00	6	46	90	143	10.18	0.28	34	3.31	1482	2	79	873	11	0.94	<5	<5	<10	320	5504	9	347	<10	34	111
205668	1361826	0.041	<1	7.26	<2	12	2	13	6.30	6	51	88	120	10.57	0.16	33	3.42	1550	<1	68	889	9	0.89	<5	<5	<10	339	6251	7	367	<10	35	112
205669	1361827	0.007	<1	7.08	<2	11	<2	16	7.00	6	52	111	107	9.99	0.37	25	3.34	1523	2	87	819	13	0.77	5	<5	<10	343	6458	9	322	<10	32	104
205670	1361828	0.009	<1	7.67	3	111	2	21	6.49	6	56	92	133	10.08	0.46	27	3.01	1940	<1	97	794	5	1.05	<5	<5	<10	240	6866	12	348	<10	32	122
205671	1361829	0.008	<1	6.17	<2	227	<2	12	6.17	5	56	78	121	8.40	0.39	26	2.64	1841	1	99	893	1	0.76	6	<5	<10	180	7621	5	344	<10	33	112
205672	1361830	0.013	1	7.92	<2	168	<2	9	6.87	6	50	103	113	9.26	0.48	26	2.48	2073	1	76	857	6	1.14	<5	<5	<10	239	6577	10	343	<10	34	121
205673	1361831	0.013	<1	7.48	<2	13	2	13	7.59	6	55	121	158	10.60	0.43	17	2.72	2073	<1	84	828	9	1.11	<5	<5	<10	324	7402	19	349	<10	33	120
205674	1361832	0.014	1	6.98	<2	9	<2	18	6.99	6	52	118	118	11.37	0.41	21	2.69	2444	<1	82	845	9	1.19	<5	<5	<10	319	6256	18	352	10	33	130
205675	1361833	0.007	<1	6.83	11	40	<2	2	6.75	6	51	124	66	9.77	0.33	18	2.60	2214	<1	81	838	5	0.91	5	<5	<10	303	6265	8	353	<10	33	125
205676	1361834	0.008	3	7.13	114	185	2	9	3.91	9	42	61	378	10.69	0.05	39	1.16	1432	4	126	274	38	7.63	<5	<5	<10	195	695	<2	54	27	12	1599

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 21, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/20/2012
 Date Completed: 08/08/2012
 Job #: 201242756
 Reference: TL12252
 Sample #: 242

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
205677	1361835	0.018	1	8.39	300	203	<2	16	2.93	4	24	55	157	4.73	0.14	48	1.16	1160	3	66	381	29	3.50	5	<5	<10	270	743	<2	65	10	11	679
205678D	1361835	0.017	1	7.69	302	186	<2	<1	2.82	4	25	54	155	4.66	0.15	45	1.12	1114	3	69	377	30	3.50	<5	<5	<10	260	689	<2	62	11	10	667
205679	1361836	0.011	2	9.91	28	186	<2	3	5.35	7	25	39	69	6.76	0.47	35	1.46	2333	5	60	647	24	2.79	<5	<5	<10	250	2851	3	99	16	17	610
205680	1361837	0.006	1	9.90	20	206	<2	9	3.68	4	27	26	29	4.89	0.42	31	1.79	1390	<1	43	859	9	1.31	<5	<5	<10	233	4252	3	137	17	14	566
205681	1361838	0.012	1	>10.00	127	167	<2	12	4.21	<4	24	26	28	4.03	0.46	29	1.75	1153	1	44	921	10	0.99	<5	<5	<10	265	3525	<2	132	<10	15	66
205682	1361839	0.013	1	8.28	6	147	<2	11	4.26	4	24	26	31	7.54	0.44	25	1.75	2472	<1	50	710	9	1.12	<5	<5	<10	251	3519	<2	103	10	15	101
205683	1361840	0.015	1	8.80	7	455	<2	14	2.83	<4	17	56	23	3.45	0.43	23	1.57	705	1	33	621	7	1.12	<5	<5	<10	339	3267	<2	120	28	19	54
205684	1361841	0.008	1	>10.00	8	510	<2	8	4.28	<4	23	89	29	3.88	0.65	47	1.35	997	5	70	751	9	1.78	<5	<5	<10	349	4449	<2	93	<10	17	98
205685	1361842	0.009	2	>10.00	2	472	2	24	3.93	<4	13	52	32	2.84	0.46	47	1.24	690	6	60	490	10	2.03	<5	<5	<10	334	2528	<2	53	<10	13	110
205686	1361843	0.006	1	>10.00	4	446	<2	19	2.82	<4	7	27	7	1.61	0.46	33	0.86	378	2	29	360	9	1.40	<5	<5	<10	333	1843	<2	37	10	8	54
205687	1361844	0.010	1	>10.00	<2	507	2	16	2.98	<4	7	30	24	1.62	0.43	33	0.84	501	4	32	388	11	1.43	<5	<5	<10	359	1623	<2	33	10	8	69
205688	1361845	<0.005	<1	9.49	<2	599	<2	7	2.43	<4	7	35	7	1.56	0.41	26	0.75	249	4	42	357	13	1.03	5	<5	<10	347	1615	<2	34	<10	7	44
205689D	1361845	<0.005	<1	8.77	4	581	<2	9	2.31	<4	8	32	7	1.53	0.46	25	0.73	246	3	41	357	9	1.00	<5	<5	<10	324	1590	<2	34	10	7	53
205690	1361846	<0.005	<1	6.71	<2	547	<2	6	2.09	<4	9	31	12	1.59	0.34	19	0.68	253	2	37	336	8	0.74	<5	<5	<10	292	1576	<2	35	<10	6	43
205691	1361847	<0.005	<1	4.51	5	506	<2	7	1.96	<4	7	35	4	1.57	0.21	16	0.62	255	4	51	339	5	0.47	<5	<5	<10	230	1422	<2	32	<10	5	47
205692	1361848	<0.005	<1	5.23	6	441	<2	7	1.68	<4	6	33	4	1.60	0.47	18	0.72	323	3	45	347	4	0.67	<5	<5	<10	265	1489	5	32	<10	5	43
205693	1361849	0.006	<1	5.06	5	566	<2	1	1.61	<4	7	38	15	1.68	0.41	18	0.76	394	5	56	355	6	0.66	<5	<5	<10	224	1486	<2	33	<10	5	44
205694	1361850	0.005	<1	4.53	2	587	<2	7	1.54	<4	8	36	5	1.53	0.45	18	0.65	298	3	50	334	3	0.61	<5	<5	<10	237	1450	<2	31	<10	5	43
205695	1361851	<0.005	<1	5.19	<2	495	<2	9	1.63	<4	6	35	4	1.60	0.64	16	0.68	294	3	44	338	8	0.58	<5	<5	<10	289	1355	<2	33	<10	5	47
205696	1361852	<0.005	<1	8.20	9	587	<2	14	1.91	<4	7	34	4	1.56	0.84	24	0.73	288	3	46	359	9	0.84	<5	<5	<10	354	1597	<2	34	12	6	58

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 21, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/20/2012
 Date Completed: 08/08/2012
 Job #: 201242756
 Reference: TL12252
 Sample #: 242

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
205697	1361853	<0.005	<1	9.59	4	419	<2	14	2.56	<4	8	38	7	1.77	0.34	26	0.84	391	6	54	406	10	1.20	<5	<5	<10	337	1773	<2	38	<10	8	32
205698	1361854	<0.005	<1	8.52	2	422	<2	<1	2.44	<4	11	49	27	2.10	0.43	25	0.86	418	6	68	397	12	1.06	<5	<5	<10	288	2095	<2	44	<10	8	49
205699	1361855	0.007	1	>10.00	<2	239	<2	24	4.53	4	26	40	30	6.23	0.44	30	1.86	1899	5	62	794	6	1.24	5	<5	<10	286	4452	3	128	<10	16	235
205700R	1361855	<0.005	<1	8.75	3	346	<2	10	4.78	<4	33	139	36	5.27	0.32	19	1.82	1509	1	86	904	5	0.95	<5	<5	<10	381	5002	6	130	<10	16	93
205701	1361856	0.006	<1	7.31	<2	247	<2	15	4.52	6	22	58	32	9.82	0.30	17	1.94	3414	2	62	814	19	0.97	<5	<5	<10	248	3382	10	110	<10	15	216
205702	1361857	0.007	1	8.82	<2	235	<2	5	4.24	4	26	36	26	6.05	0.47	25	1.81	1786	3	61	792	6	0.98	<5	<5	<10	273	4181	<2	128	<10	15	235

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/03/2012
 Date Completed:
 Job #: 201242455
 Reference: TL 12 253
 Sample #: 219

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
184460	1361858	0.010	<1	7.28	9	409	<2	20	2.69	<4	16	40	20	3.26	0.10	27	1.11	609	<1	51	485	10	0.49	<5	<5	<10	271	3113	2	89	<10	12	53
184461	1361859	0.007	<1	6.14	2	521	<2	36	1.67	<4	6	48	4	1.59	0.08	26	0.70	291	<1	80	353	9	0.32	<5	<5	<10	245	1628	2	32	<10	5	38
184462	1361860	4.644	68	4.54	37	494	<2	52	1.47	20	14	34	49	3.23	0.10	11	0.98	525	<1	27	528	586	0.59	67	<5	237	262	2040	3	92	54	13	1900
184463	1361861	0.006	<1	7.44	<2	586	<2	35	2.81	<4	14	74	11	3.06	0.18	32	1.14	578	3	112	424	13	0.40	<5	<5	<10	263	2599	7	79	<10	10	57
184464	1361862	0.013	<1	5.79	<2	46	<2	37	6.18	<4	52	103	88	10.02	0.14	17	2.88	1857	<1	121	934	16	0.47	<5	<5	<10	272	7961	3	330	<10	35	121
184465	1361863	0.036	<1	6.93	4	171	<2	39	7.10	<4	62	90	195	10.90	0.21	27	3.34	2078	<1	108	925	8	1.26	5	<5	<10	277	8503	8	343	<10	35	115
184466	1361864	0.007	<1	5.98	<2	17	<2	43	5.56	<4	56	93	109	10.57	0.07	25	3.28	1570	<1	112	929	10	0.42	<5	5	<10	326	8569	<2	361	<10	36	118
184467	1361865	0.011	<1	5.38	<2	46	<2	40	4.74	<4	42	89	49	8.63	0.11	33	2.64	1430	<1	99	792	6	0.50	<5	<5	10	179	7100	<2	291	<10	30	129
184468	1361866	0.009	<1	5.00	2	40	<2	65	4.59	<4	42	115	48	8.63	0.07	30	2.56	1450	6	156	793	10	0.45	5	<5	<10	175	7055	4	286	<10	29	121
184469	1361867	0.014	<1	6.85	<2	91	<2	30	6.40	<4	56	104	98	10.05	0.12	34	3.20	1673	<1	132	787	11	0.58	<5	<5	<10	270	8021	7	316	<10	31	112
184470D	1361867	0.018	<1	7.44	<2	97	<2	42	6.35	<4	55	102	95	9.86	0.26	35	3.16	1644	<1	134	764	12	0.59	7	<5	<10	274	8025	8	313	<10	31	117
184471	1361868	0.012	<1	6.97	9	108	<2	30	5.98	<4	49	75	90	8.80	0.29	22	2.80	1751	<1	80	783	12	0.50	<5	<5	<10	242	7463	3	312	<10	30	103
184472	1361869	0.009	<1	5.56	<2	122	<2	39	5.90	<4	52	108	92	9.38	0.23	22	2.83	1725	<1	132	881	13	0.43	5	<5	<10	215	7005	7	316	<10	33	110
184473	1361870	0.008	<1	6.48	<2	145	<2	33	6.71	<4	54	105	76	10.09	0.22	24	3.00	1818	<1	124	867	14	0.53	6	<5	<10	228	7607	8	329	<10	34	119
184474	1361871	0.010	<1	6.38	<2	140	<2	56	6.20	<4	53	104	94	10.03	0.23	28	2.96	1707	<1	119	851	11	0.55	<5	<5	<10	248	7457	2	315	<10	33	108
184475	1361872	0.012	<1	5.60	3	63	<2	61	5.76	<4	49	94	92	8.83	0.08	21	2.72	1606	<1	100	907	5	0.45	<5	<5	<10	217	7006	<2	313	<10	32	115
184476	1361873	0.021	<1	6.56	4	115	<2	36	5.92	<4	55	100	100	9.12	0.13	31	2.75	1870	<1	106	947	10	0.52	<5	<5	<10	255	8572	8	361	<10	35	122
184477	1361874	0.006	<1	5.01	<2	71	<2	51	6.02	<4	52	94	133	9.35	0.10	31	2.76	1798	<1	101	866	14	0.59	5	<5	<10	232	7967	14	338	<10	33	108
184478	1361875	0.013	<1	5.65	9	85	<2	43	7.20	<4	48	86	125	9.03	0.15	28	2.77	1811	<1	92	814	13	0.59	<5	5	<10	292	8622	<2	302	<10	33	156
184479	1361876	0.010	<1	6.06	2	61	<2	73	5.74	<4	52	94	90	9.82	0.11	21	2.95	1646	<1	107	955	9	0.58	<5	<5	<10	239	7876	<2	314	<10	35	130

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/03/2012
 Date Completed:
 Job #: 201242455
 Reference: TL 12 253
 Sample #: 219

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm	
184480	1361877	0.012	<1	5.33	3	775	<2	76	9.39	<4	45	75	92	8.44	0.19	14	2.59	2321	<1	81	843	9	1.26	<5	<5	<10	1025	7951	4	255	<10	31	147	
184481D	1361877	0.015	<1	5.13	<2	781	<2	26	9.30	<4	45	74	90	8.34	0.23	13	2.57	2276	<1	79	821	15	1.24	<5	<5	<10	1015	7763	5	254	<10	30	146	
184482	1361878	0.014	<1	6.15	6	314	<2	45	6.44	<4	55	94	104	10.25	0.10	16	2.73	2265	<1	108	873	10	1.04	<5	<5	<10	454	9466	5	340	<10	34	153	
184483	1361879	0.012	<1	5.27	3	255	<2	28	5.65	<4	47	80	143	7.82	0.35	21	1.84	1639	<1	108	622	11	1.92	<5	<5	<10	363	5511	<2	201	<10	23	163	
184484	1361880	<0.005	<1	6.79	10	453	<2	38	2.72	<4	18	55	22	3.62	0.20	16	1.59	742	<1	33	622	9	0.30	<5	6	<10	332	3211	5	124	22	17	52	
184485	1361881	0.011	<1	6.47	<2	429	<2	35	3.92	<4	37	102	131	7.50	0.15	59	1.89	1290	3	139	745	15	1.14	<5	<5	<10	283	5335	<2	181	<10	23	242	
184486	1361882	0.009	<1	6.45	8	109	<2	59	6.87	<4	54	107	89	10.43	0.13	22	2.96	1737	<1	146	935	11	0.61	5	<5	<10	230	8162	9	321	<10	36	134	
184487	1361883	0.008	<1	6.93	<2	39	<2	28	6.83	<4	53	83	91	10.21	0.11	31	3.06	1479	<1	98	943	11	0.60	5	<5	<10	197	7986	6	331	<10	37	109	
184488	1361884	0.011	<1	6.30	<2	23	<2	53	6.26	<4	51	74	80	10.21	0.18	26	3.05	1460	<1	80	899	9	0.47	<5	<5	<10	158	7870	17	323	<10	36	114	
184489	1361885	0.008	<1	6.17	2	10	<2	37	6.14	<4	54	72	69	10.12	0.17	32	3.05	1479	<1	79	932	11	0.50	6	<5	<10	185	8444	6	328	<10	36	114	
184490	1361886	0.009	<1	5.93	5	14	<2	53	6.33	<4	54	71	73	10.27	0.25	26	3.07	1546	<1	75	923	7	0.50	6	<5	<10	186	8299	<2	331	<10	37	119	
184491	1361887	0.009	<1	6.09	7	10	<2	32	6.68	<4	52	78	86	10.14	0.22	24	3.21	1607	<1	83	880	10	0.47	5	<5	<10	194	7825	7	330	<10	35	117	
184492D	1361887	0.007																																
184493	1361888	0.012	<1	6.22	<2	8	<2	50	6.07	<4	51	90	89	10.43	0.13	24	3.56	1573	<1	89	888	9	0.35	<5	<5	<10	211	7554	9	340	<10	34	102	
184494	1361889	0.008	<1	6.68	4	17	<2	48	5.43	<4	51	84	89	10.04	0.21	28	3.36	1454	<1	85	844	7	0.42	<5	<5	<10	224	7728	5	336	<10	33	99	
184495	1361890	0.064	<1	5.13	9	7	<2	40	4.58	<4	50	73	76	9.55	0.30	28	3.45	1312	<1	69	806	8	0.30	7	5	<10	183	7215	9	337	<10	32	88	
184496	1361891	0.066	<1	7.02	3	542	<2	12	3.19	<4	7	29	4	1.63	0.12	24	0.78	346	<1	41	306	13	0.26	<5	<5	<10	311	1596	7	34	<10	6	25	
184497	1361892	<0.005	<1	5.49	4	10	<2	38	5.35	<4	52	77	112	10.19	0.21	26	3.30	1402	<1	87	917	11	0.40	<5	<5	<10	200	7850	<2	349	<10	35	93	
184498	1361893	0.012	<1	6.67	3	7	<2	34	6.00	<4	55	59	93	10.38	0.17	27	3.12	1586	<1	71	950	6	0.40	6	<5	<10	203	9254	<2	364	<10	37	104	
184499	1361894	0.007	<1	6.14	3	4	<2	40	5.88	<4	53	46	83	10.93	0.10	30	3.04	1584	<1	70	1006	11	0.40	6	8	<10	206	8903	<2	376	<10	38	110	

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/03/2012
 Date Completed:
 Job #: 201242455
 Reference: TL 12 253
 Sample #: 219

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
184500	1361895	0.019	<1	5.50	7	16	<2	22	6.22	<4	51	79	101	10.08	0.08	23	3.06	1507	<1	89	889	10	0.33	5	<5	<10	252	7974	<2	315	<10	34	109
184501	1361896	0.012	<1	5.86	5	39	<2	37	5.89	<4	54	111	91	9.42	0.21	31	2.93	1552	<1	101	844	14	0.34	<5	<5	<10	275	7869	6	331	<10	32	106
184502	1361897	0.022	<1	6.42	4	82	<2	46	5.91	<4	56	111	145	9.17	0.18	25	2.90	1605	<1	101	831	11	0.62	<5	<5	10	210	7697	3	324	<10	31	149
184503D	1361897	0.015	<1	5.54	2	72	<2	33	5.75	<4	54	112	148	9.07	0.21	22	2.86	1577	<1	101	837	15	0.60	<5	6	<10	194	7085	7	313	<10	31	154
184504	1361898	0.008	<1	5.47	<2	122	<2	40	5.80	<4	51	104	100	9.35	0.21	22	3.17	1491	<1	102	744	18	0.37	<5	<5	<10	231	5961	13	289	<10	29	117
184505	1361899	0.022	<1	5.85	<2	67	<2	49	5.87	<4	50	94	75	9.35	0.19	32	3.29	1465	<1	97	716	12	0.35	<5	<5	<10	274	6035	7	296	<10	28	90
184506	1361900	2.000	<1	7.18	13	457	<2	39	2.56	<4	17	53	30	3.78	0.09	19	1.59	734	<1	35	604	11	0.31	<5	<5	<10	312	3131	6	124	21	17	55
184507	1361901	0.013	<1	5.68	<2	44	<2	41	5.98	<4	52	81	77	9.38	0.16	21	3.09	1488	<1	102	721	14	0.33	<5	<5	<10	290	6936	2	292	<10	28	101
184508	1361902	0.010	<1	5.83	4	44	<2	26	5.99	<4	55	79	87	9.76	0.13	31	3.16	1695	<1	109	760	9	0.35	<5	<5	<10	240	7066	<2	309	<10	30	111
184509	1361903	0.011	<1	6.92	3	85	<2	61	6.69	<4	58	84	121	9.85	0.07	21	2.85	2130	<1	102	892	12	0.44	5	<5	<10	228	9002	5	345	<10	35	107
184510	1361904	<0.005	<1	5.92	2	165	<2	50	6.36	<4	50	93	87	9.70	0.28	20	2.18	2850	<1	100	822	11	0.52	7	<5	<10	203	7993	7	301	<10	34	108
184511	1361905	0.016	<1	6.28	<2	23	<2	27	6.41	<4	58	124	196	11.10	0.29	18	2.75	2379	<1	100	842	10	0.69	<5	<5	<10	231	7978	<2	335	<10	32	131
184512	1361906	0.015	<1	6.33	<2	14	<2	45	6.51	<4	56	118	192	10.82	0.27	17	2.70	2378	<1	90	821	12	0.72	6	<5	<10	242	7325	<2	331	<10	31	127
184513	1361907	0.012	<1	6.30	17	4	<2	64	6.86	<4	56	122	83	10.69	0.23	17	2.78	2331	<1	92	808	11	0.40	5	<5	<10	338	8182	13	339	<10	32	109
184514D	1361907	0.014	<1	6.24	<2	4	<2	28	6.80	<4	54	119	82	10.59	0.22	17	2.77	2283	<1	83	807	11	0.41	<5	<5	<10	333	7939	3	334	<10	31	112
184515	1361908	0.012	<1	6.87	4	29	<2	45	7.03	4	53	119	88	10.22	0.26	21	2.83	2195	<1	84	829	14	0.51	<5	6	<10	285	7275	2	340	<10	33	206
184516	1361909	0.322	<1	6.58	25	81	<2	50	1.83	7	78	93	392	14.81	0.13	39	1.20	815	<1	210	355	25	9.46	<5	5	10	176	2369	7	96	14	13	981
184517	1361910	0.020	<1	6.42	11	322	<2	55	1.78	4	52	66	280	6.03	0.13	27	0.85	735	<1	116	330	35	4.16	<5	<5	10	227	1604	6	76	18	12	1402
184518	1361911	0.022	<1	7.38	561	284	<2	46	1.87	5	41	79	233	5.49	0.10	34	1.06	907	<1	110	734	30	3.63	<5	9	10	292	1107	<2	87	21	13	1841
184519	1361912	<0.005	<1	7.99	257	134	<2	49	4.46	<4	27	43	66	5.65	0.21	29	2.04	1694	<1	76	754	13	1.43	<5	<5	<10	265	3465	6	127	<10	14	185

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/03/2012
 Date Completed:
 Job #: 201242455
 Reference: TL 12 253
 Sample #: 219

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
184520	1361913	0.097	<1	8.53	9	114	<2	46	5.31	<4	26	46	54	9.61	0.17	28	2.14	3325	<1	80	683	12	1.44	<5	<5	<10	219	4046	<2	117	<10	16	252
184521	1361914	0.017	<1	8.39	5	202	<2	40	4.20	<4	27	105	23	5.31	<0.01	35	1.92	1130	<1	87	786	14	0.38	<5	5	<10	294	4700	7	115	<10	12	139
184522	1361915	0.024	<1	7.27	6	302	<2	37	4.31	<4	26	141	21	6.22	0.13	32	1.43	1971	<1	119	640	12	0.60	<5	5	<10	260	3958	<2	84	<10	11	83
184523	1361916	0.034	<1	6.32	2	113	<2	59	5.17	<4	32	200	26	10.73	0.08	28	2.19	3833	<1	136	710	17	0.67	8	6	<10	230	4643	6	112	<10	14	119
184524	1361917	0.006	<1	6.57	<2	378	<2	31	2.53	<4	21	190	18	3.33	0.15	31	1.60	901	<1	105	608	16	0.30	<5	7	<10	216	2940	6	73	<10	9	71
184525R	1361917	<0.005	<1	6.32	5	392	<2	36	2.57	<4	22	182	19	3.22	0.12	31	1.61	843	<1	91	607	14	0.30	<5	<5	<10	217	2956	9	73	<10	9	70
184526	1361918	<0.005	<1	7.07	10	627	<2	41	2.06	<4	9	62	4	2.02	0.16	20	0.71	396	2	61	385	10	0.38	5	<5	<10	233	1990	<2	42	<10	6	123
184527	1361919	0.014	<1	6.90	<2	558	<2	37	2.23	<4	9	56	5	1.89	0.04	24	0.61	383	3	48	345	8	0.40	<5	<5	<10	243	1987	8	42	<10	4	91
184528	1361920	0.013	<1	5.49	6	514	<2	36	2.65	<4	18	69	23	3.78	0.08	7	1.39	773	<1	33	627	10	0.24	<5	<5	<10	310	3464	6	130	20	15	71
184529	1361921	0.009	<1	5.35	<2	655	<2	39	3.41	<4	7	46	4	1.70	0.10	18	0.49	371	2	42	298	9	0.27	<5	<5	<10	312	1705	<2	37	<10	4	41
184530	1361922	0.007	<1	5.00	7	597	<2	52	1.80	<4	6	34	2	1.53	<0.01	18	0.52	253	<1	27	287	7	0.21	<5	<5	<10	287	1568	<2	33	<10	3	39
184531	1361923	0.010	<1	5.21	10	641	<2	75	1.77	<4	7	40	1	1.54	<0.01	22	0.47	232	<1	30	280	10	0.26	<5	<5	<10	311	1620	8	34	<10	3	44
184532	1361924	0.010	<1	5.46	2	601	<2	49	1.67	<4	7	56	8	1.64	0.02	18	0.55	235	2	68	320	8	0.24	<5	<5	<10	293	1525	<2	33	<10	4	35
184533	1361925	0.005	<1	6.70	3	612	<2	11	1.92	<4	6	36	6	1.51	<0.01	18	0.55	237	<1	28	316	4	0.33	<5	<5	<10	277	1548	<2	33	<10	5	43
184534	1361926	0.010	<1	5.11	8	615	<2	49	1.76	<4	6	59	6	1.69	0.20	17	0.56	254	<1	69	324	8	0.29	<5	<5	<10	239	1517	3	34	<10	4	40
184535	1361927	0.011	<1	7.05	5	406	<2	35	2.60	<4	8	39	38	1.79	0.24	17	0.64	424	<1	29	319	10	0.55	<5	<5	<10	277	1519	2	33	<10	5	37
184536D	1361927	0.011	<1	6.26	<2	395	<2	42	2.56	<4	7	32	36	1.76	0.29	16	0.63	421	<1	29	313	12	0.50	<5	<5	<10	275	1476	<2	32	<10	5	34
184537	1361928	0.008	<1	6.40	2	342	2	43	2.47	<4	5	60	4	1.48	0.24	16	0.52	398	5	73	340	7	0.41	<5	<5	<10	208	1317	5	30	<10	5	20
184538	1361929	0.010	<1	6.86	7	379	<2	29	2.38	<4	7	47	4	1.81	0.05	27	0.92	436	<1	71	340	7	0.37	<5	<5	<10	241	1494	8	34	<10	5	30
184539	1361930	0.008	<1	5.99	3	497	<2	35	2.14	<4	7	37	6	1.60	0.10	23	0.70	284	<1	48	316	9	0.30	5	<5	<10	244	1556	2	33	<10	5	33

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/03/2012
 Date Completed:
 Job #: 201242455
 Reference: TL 12 253
 Sample #: 219

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
184540	1361931	<0.005	<1	6.15	8	447	<2	27	2.33	<4	7	37	5	1.68	0.03	24	0.73	359	<1	50	330	7	0.36	<5	<5	<10	255	1640	5	34	<10	5	31
184541	1361932	0.006	<1	6.13	9	328	<2	28	3.24	<4	7	40	2	1.85	0.02	25	0.94	582	<1	49	325	10	0.41	<5	<5	<10	290	1647	7	34	<10	5	21
184542	1361933	0.010	<1	4.34	<2	413	<2	44	1.83	<4	6	49	4	1.53	<0.01	13	0.50	298	<1	50	296	12	0.26	<5	10	<10	230	1503	3	32	<10	4	24
184543	1361934	0.006	<1	5.13	5	532	<2	34	2.08	<4	8	52	7	1.82	<0.01	17	0.54	290	<1	54	307	8	0.23	<5	<5	<10	259	1792	<2	39	<10	4	41
184544	1361935	0.007	<1	6.97	9	384	<2	44	3.01	<4	28	79	77	5.35	0.11	29	1.22	1133	<1	83	569	10	1.33	<5	<5	11	289	3550	<2	82	<10	10	526
184545	1361936	0.009	<1	6.50	5	292	2	34	3.89	<4	21	90	61	7.28	<0.01	26	1.62	1718	1	90	439	13	1.36	5	<5	<10	277	3363	<2	75	<10	12	181
184546	1361937	0.013	<1	4.82	<2	216	<2	42	3.66	<4	20	104	44	7.45	0.11	17	1.44	1689	<1	88	549	11	1.43	<5	9	<10	268	2883	2	54	<10	12	129
184547D	1361937	0.010	<1	5.38	7	223	<2	59	3.63	<4	19	106	43	7.31	0.19	18	1.40	1681	1	89	540	11	1.42	<5	<5	<10	267	2988	<2	54	<10	12	123
184548	1361938	0.006	<1	6.55	8	502	<2	36	2.09	<4	6	43	9	1.64	0.02	21	0.54	367	<1	43	343	9	0.38	<5	<5	<10	237	1760	<2	32	<10	5	35
184549	1361939	0.012	<1	7.19	<2	510	<2	42	2.26	<4	7	43	7	1.65	0.11	25	0.83	479	2	43	348	4	0.41	<5	<5	<10	244	1682	7	31	<10	5	24
184550	1361940	0.244	<1	0.42	453	>5000	<2	26	0.95	<4	8	17	31	3.08	<0.01	5	0.27	<100	4	13	<100	23	0.56	23	<5	<10	141	796	11	15	40	7	16
184551	1361941	<0.005	<1	6.62	6	485	<2	30	2.33	<4	6	38	5	1.60	<0.01	30	0.67	358	<1	53	332	10	0.33	<5	10	<10	308	1662	<2	32	<10	4	28
184552	1361942	0.005	<1	6.11	5	400	<2	24	2.55	<4	7	39	3	1.70	<0.01	25	0.70	507	<1	54	345	8	0.38	<5	<5	<10	332	1674	<2	32	<10	5	28
184553	1361943	0.006	<1	5.77	<2	382	<2	36	2.51	<4	8	42	16	1.93	<0.01	29	0.77	475	<1	51	339	9	0.41	<5	<5	<10	331	1941	<2	36	<10	5	35
184554	1361944	0.012	<1	5.83	3	596	<2	33	1.90	<4	19	41	95	2.86	0.28	27	0.83	383	<1	61	360	12	0.65	<5	<5	<10	321	1998	2	45	<10	6	84
184555	1361945	<0.005	<1	6.33	<2	433	<2	44	2.21	<4	11	40	51	2.06	0.06	29	0.72	356	<1	54	334	10	0.39	<5	<5	<10	294	1955	2	43	<10	5	48
184556	1361946	<0.005	<1	5.76	3	424	<2	43	2.03	<4	10	29	37	1.97	0.21	24	0.72	347	<1	36	362	9	0.33	<5	<5	<10	271	1952	<2	41	<10	5	49
184557	1361947	<0.005	<1	6.60	6	245	<2	21	3.09	<4	27	141	35	3.76	1.21	37	1.60	741	<1	94	682	10	0.56	<5	<5	<10	285	4088	<2	100	<10	11	65
184558D	1361947	<0.005	<1	6.29	<2	220	<2	55	2.69	<4	26	139	34	3.56	0.08	31	1.64	669	<1	89	684	6	0.51	<5	<5	<10	242	3364	8	94	<10	11	62
184559	1361948	<0.005	<1	6.77	3	232	<2	31	4.89	<4	42	318	41	5.85	0.12	30	2.65	1443	<1	156	797	4	0.70	<5	<5	<10	315	4696	8	131	<10	13	92

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/03/2012
 Date Completed:
 Job #: 201242455
 Reference: TL 12 253
 Sample #: 219

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
184560	1361949	<0.005	<1	7.54	6	335	<2	20	3.75	<4	19	36	10	4.17	0.08	26	1.22	1163	<1	61	684	11	0.37	<5	<5	<10	335	3926	<2	89	<10	11	58
184561	1361950	<0.005	<1	7.39	5	547	<2	26	2.14	<4	7	27	1	1.51	0.15	25	0.71	289	<1	35	343	7	0.26	<5	<5	<10	356	1710	4	32	<10	6	28
184562	1361951	<0.005	<1	6.22	<2	567	<2	50	1.98	<4	8	34	23	1.79	0.08	23	0.72	355	<1	52	334	6	0.24	<5	5	<10	319	1782	<2	38	<10	6	30
184563	1361952	<0.005	<1	5.80	<2	329	<2	45	2.57	<4	14	28	16	2.92	<0.01	24	0.88	763	<1	41	489	11	0.30	<5	<5	<10	302	3169	<2	63	<10	7	29
184564	1361953	<0.005	<1	6.60	<2	344	<2	32	2.58	<4	16	31	28	3.64	0.15	28	1.08	801	<1	50	536	9	0.39	<5	<5	<10	308	3424	3	70	<10	8	45
184565	1361954	<0.005	<1	7.39	5	260	<2	27	4.91	<4	38	35	50	8.06	0.16	31	1.96	2416	<1	78	1064	10	0.64	<5	<5	<10	374	6924	9	162	<10	16	86
184566	1361955	<0.005	<1	7.11	7	206	<2	31	6.12	<4	38	39	39	9.40	0.26	28	2.14	4098	<1	81	1165	8	0.50	<5	<5	<10	371	6940	<2	164	<10	17	95
184567	1361956	<0.005	<1	6.10	4	357	<2	57	5.23	<4	34	38	25	8.59	0.26	35	1.90	3173	<1	72	953	7	0.44	<5	<5	<10	305	5933	8	145	<10	16	89
184568	1361957	0.010	<1	6.25	3	216	<2	37	5.82	6	59	230	82	16.10	0.17	30	2.11	3974	<1	204	1299	15	4.48	10	<5	<10	346	7661	7	169	<10	25	158
184569D	1361957	0.010	<1	6.38	7	208	<2	51	5.65	5	55	225	80	15.61	0.09	29	2.08	3738	<1	203	1261	14	4.36	<5	<5	<10	336	6682	<2	165	<10	25	151
184570	1361958	<0.005	<1	7.88	9	323	<2	26	6.64	<4	56	331	34	7.43	0.17	35	3.30	1535	<1	183	1557	9	0.39	<5	<5	<10	362	8313	11	203	<10	26	152
184571	1361959	0.006	<1	7.05	<2	195	<2	52	4.16	<4	68	303	52	8.14	0.06	25	1.62	1673	<1	222	1563	9	2.11	<5	<5	<10	313	7609	2	193	<10	28	135
184572	1361960	<0.005	<1	4.89	3	402	<2	33	2.38	<4	16	51	20	3.34	0.07	11	1.43	683	<1	30	583	9	0.25	<5	<5	<10	293	2954	4	114	19	15	40
184573	1361961	<0.005	<1	8.04	<2	182	<2	46	4.96	<4	57	302	44	7.65	0.18	30	2.35	1864	<1	199	1530	7	0.55	<5	6	<10	399	9247	10	195	<10	28	132
184574	1361962	<0.005	<1	7.14	6	188	<2	40	4.66	<4	53	319	55	5.67	0.30	26	2.24	818	<1	203	1521	6	0.42	<5	<5	<10	503	5360	2	197	<10	27	120
184575	1361963	<0.005	<1	7.71	<2	149	3	57	4.39	<4	52	306	39	5.55	0.16	33	1.93	906	<1	198	1407	2	0.47	<5	<5	10	372	8199	5	186	<10	23	116
184576	1361964	<0.005	<1	6.64	7	165	<2	19	4.40	<4	55	319	47	5.84	0.32	31	2.23	999	<1	191	1411	3	0.47	<5	<5	<10	327	8442	4	191	<10	25	120
184577	1361965	0.008	<1	6.54	<2	178	<2	48	5.36	<4	54	319	51	7.97	0.13	30	1.77	1806	<1	201	1301	7	1.26	<5	<5	<10	318	9085	<2	204	<10	23	123
184578	1361966	0.010	<1	6.37	<2	174	<2	49	5.20	<4	54	322	49	7.72	0.11	28	1.79	1795	<1	200	1353	7	1.05	5	<5	<10	311	8880	4	197	<10	24	126
184579	1361967	0.050	<1	6.50	6	120	<2	36	5.05	4	74	197	103	11.57	0.12	31	2.00	1087	<1	173	997	13	6.85	<5	<5	<10	295	5348	8	161	<10	19	133

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/03/2012
 Date Completed:
 Job #: 201242455
 Reference: TL 12 253
 Sample #: 219

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
184580D	1361967	0.030	<1	6.73	6	111	<2	48	5.01	<4	74	194	103	11.67	0.14	29	2.02	1070	<1	178	1001	13	6.97	6	<5	<10	290	5127	<2	156	<10	20	137
184581	1361968	0.026	<1	8.30	6	177	<2	44	6.06	<4	75	301	52	8.64	<0.01	40	2.13	1042	<1	187	1249	11	4.39	<5	<5	<10	297	7168	2	203	<10	20	166
184582	1361969	0.013	<1	7.46	6	166	<2	49	3.51	<4	54	273	73	6.39	0.14	49	1.71	755	<1	211	974	10	3.11	<5	5	<10	274	4415	7	186	<10	13	171
184583	1361970	0.010	<1	7.67	11	155	<2	51	4.41	<4	56	259	55	6.57	0.06	42	1.80	931	<1	196	1081	13	3.38	5	5	<10	270	4865	<2	188	<10	13	220
184584	1361971	0.039	<1	6.07	41	72	2	65	3.01	8	92	188	95	18.06	0.08	28	1.54	1229	<1	190	525	21	>10.00	9	<5	<10	179	2709	10	113	<10	9	231
184585	1361972	0.005	<1	7.58	7	136	<2	35	2.75	<4	52	262	79	7.07	0.23	60	1.68	662	<1	220	923	16	3.76	<5	<5	<10	225	3975	3	156	<10	9	142
184586	1361973	0.012	<1	8.74	<2	141	<2	38	5.95	<4	68	357	93	6.11	0.22	53	2.18	1269	<1	259	1092	12	1.73	<5	<5	<10	258	5931	12	199	<10	18	156
184587	1361974	0.012	<1	8.83	4	172	<2	46	4.32	<4	72	348	83	5.96	0.16	61	2.21	1111	<1	218	964	10	1.94	<5	<5	<10	245	7431	10	206	<10	13	120
184588	1361975	0.012	<1	8.25	8	197	<2	48	4.83	<4	67	367	82	5.40	0.21	68	2.20	1025	<1	215	1068	7	1.21	<5	<5	<10	260	7176	6	215	<10	16	124
184589	1361976	0.012	<1	7.53	4	174	<2	43	5.05	<4	65	372	76	5.33	0.06	62	2.26	1176	<1	210	1128	11	0.91	<5	<5	10	269	7403	5	210	<10	15	141
184590	1361977	0.008	<1	7.09	2	267	<2	31	4.06	<4	19	108	24	2.35	0.03	45	1.03	660	<1	82	603	10	0.50	<5	<5	<10	277	3188	<2	70	<10	9	36
184591R	1361977	0.009	<1	7.60	<2	269	<2	36	4.15	<4	19	114	25	2.41	0.07	46	1.08	665	<1	95	631	8	0.46	<5	<5	<10	279	3227	5	71	<10	10	39
184592	1361978	<0.005	<1	4.58	7	562	<2	11	3.62	<4	5	34	2	1.41	0.04	25	0.37	270	<1	35	309	8	0.24	<5	7	<10	312	1631	<2	28	<10	3	93
184593	1361979	0.006	<1	4.14	4	733	<2	34	3.00	<4	6	32	<1	1.45	0.13	20	0.32	221	<1	34	315	7	0.23	<5	<5	<10	316	1738	3	28	<10	2	45
184594	1361980	4.785	68	2.83	38	515	<2	31	1.30	20	14	43	50	3.39	0.05	3	0.72	513	<1	26	494	576	0.58	75	<5	233	231	2087	<2	96	55	10	1902
184595	1361981	0.010	<1	3.53	<2	547	<2	26	3.90	<4	7	60	3	1.67	0.06	17	0.36	282	3	60	317	16	0.34	<5	<5	<10	385	1931	2	37	<10	3	42
184596	1361982	0.010	<1	3.95	<2	385	<2	36	3.72	<4	7	36	6	1.59	<0.01	13	0.40	462	<1	40	308	7	0.35	<5	<5	<10	327	1854	<2	35	<10	3	29
184597	1361983	0.022	<1	4.73	8	463	<2	42	4.19	<4	60	368	68	4.74	<0.01	46	1.40	832	<1	204	1244	7	0.53	<5	<5	<10	327	8987	<2	197	<10	12	112
184598	1361984	0.011	<1	6.29	<2	313	<2	30	6.03	<4	58	412	49	4.98	0.13	25	1.69	1066	<1	222	1543	7	0.30	<5	<5	<10	316	6768	7	180	<10	20	109
184599	1361985	0.006	<1	6.33	<2	317	<2	44	6.71	<4	61	422	59	5.25	<0.01	12	1.42	1486	<1	228	1491	10	0.41	<5	<5	<10	344	7418	7	184	<10	20	103

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/03/2012
 Date Completed:
 Job #: 201242455
 Reference: TL 12 253
 Sample #: 219

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
184600	1361986	<0.005	<1	6.96	8	332	<2	60	6.59	<4	61	436	58	5.20	0.19	13	1.45	1439	<1	236	1482	6	0.38	<5	5	<10	353	7310	<2	184	<10	22	97
184601	1361987	0.008	<1	7.52	6	331	<2	35	5.18	<4	54	425	45	4.64	0.25	13	1.23	1332	3	241	1487	7	0.39	<5	<5	<10	333	6820	5	178	<10	20	74
184602D	1361987	0.005	<1	7.71	<2	343	<2	42	5.23	<4	55	424	43	4.61	0.29	14	1.24	1343	<1	216	1468	6	0.40	<5	5	<10	337	6973	5	179	<10	20	75
184603	1361988	0.008	<1	7.44	3	274	<2	43	7.15	<4	57	447	59	5.95	0.17	9	1.71	2172	<1	219	1588	8	0.46	<5	<5	<10	278	7633	2	174	<10	20	61
184604	1361989	<0.005	<1	6.30	2	282	<2	32	6.31	<4	59	504	58	5.53	<0.01	17	1.84	1607	<1	236	1738	4	0.35	6	<5	<10	307	6487	3	189	<10	20	80
184605	1361990	0.007	<1	4.98	2	311	<2	28	7.35	<4	63	347	101	7.49	0.10	20	1.90	2276	<1	208	1176	7	0.56	<5	8	<10	254	7441	4	219	<10	18	92
184606	1361991	<0.005	<1	5.44	<2	272	<2	29	6.70	<4	62	428	54	6.32	0.15	25	2.56	2066	<1	221	1343	9	0.38	<5	<5	<10	237	6329	10	210	<10	18	76
184607	1361992	0.007	<1	5.07	4	439	<2	17	4.98	<4	66	454	70	6.02	0.08	39	2.26	1551	<1	229	1389	7	0.35	<5	<5	<10	204	6974	11	219	<10	15	109
184608	1361993	0.007	<1	5.68	2	520	<2	45	7.05	<4	65	492	65	6.40	0.17	27	2.06	1886	<1	215	1439	9	0.33	<5	<5	<10	282	7901	17	232	<10	17	261
184609	1361994	0.008	<1	5.39	<2	423	<2	39	7.34	<4	51	241	37	7.55	0.08	30	2.30	2681	<1	139	2139	10	0.37	<5	<5	<10	257	8933	3	209	<10	20	93
184610	1361995	0.020	<1	4.95	5	241	<2	52	5.49	<4	51	350	93	9.53	0.06	29	2.80	3456	<1	168	1402	11	0.70	<5	<5	<10	136	5586	<2	177	<10	18	178
184611	1361996	0.009	<1	5.53	4	223	<2	48	7.15	<4	42	299	44	7.68	0.04	12	2.00	3642	<1	157	1195	10	0.42	<5	<5	<10	197	4641	14	153	291	19	75
184612	1361997	0.006	<1	6.41	4	348	<2	22	6.95	<4	55	337	82	8.44	0.10	12	1.90	3364	<1	192	1430	10	0.55	7	7	<10	225	5623	<2	159	<10	19	114
184613D	1361997	0.014	<1	6.34	5	364	<2	28	7.32	<4	59	356	87	8.92	0.07	13	2.01	3594	<1	208	1501	17	0.56	<5	<5	<10	235	6139	2	170	<10	20	127
184614	1361998	0.008	<1	6.84	10	305	<2	48	7.35	<4	53	327	49	8.47	0.21	11	2.19	3587	<1	197	1384	9	0.38	<5	<5	<10	240	5640	7	157	<10	19	199
184615	1361999	0.007	<1	5.84	8	169	<2	15	5.75	<4	45	188	42	6.86	0.16	18	2.17	2209	<1	108	1082	10	0.78	<5	<5	<10	166	7043	9	165	<10	19	205
184616	1362000	<0.005	<1	4.51	8	450	<2	26	2.45	<4	18	65	22	3.55	0.04	4	1.33	737	<1	32	602	6	0.23	<5	6	<10	280	3169	7	122	18	15	48
184617	1408701	0.015	<1	5.69	4	165	<2	40	5.15	<4	36	160	48	6.73	<0.01	24	2.31	1887	<1	81	1019	9	0.80	6	<5	<10	169	6066	5	189	<10	19	170
184618	1408702	0.005	<1	5.65	6	246	<2	48	4.36	<4	33	160	36	4.89	0.23	26	1.82	1547	<1	74	978	9	0.53	<5	6	<10	179	6430	2	182	<10	19	194
184619	1408703	0.021	<1	5.27	10	118	<2	43	4.60	<4	45	164	90	8.28	0.09	20	2.24	1716	<1	99	954	13	2.41	<5	<5	<10	157	5989	4	168	<10	19	424

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/03/2012
 Date Completed:
 Job #: 201242455
 Reference: TL 12 253
 Sample #: 219

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
184620	1408704	0.017	<1	4.51	4	116	<2	28	4.58	<4	44	206	78	7.02	<0.01	12	1.97	1505	<1	112	899	13	1.85	<5	<5	<10	159	5399	8	159	<10	19	363
184621	1408705	0.015	<1	5.82	5	165	<2	23	5.09	<4	35	177	68	6.24	0.13	19	2.22	1699	<1	84	969	17	1.10	<5	<5	<10	207	6905	6	169	<10	20	272
184622	1408706	0.014	<1	5.83	2	158	<2	25	5.05	<4	34	166	69	5.84	0.06	17	2.20	1646	<1	77	996	15	0.85	<5	5	<10	208	6752	6	169	<10	21	225
184623	1408707	0.079	<1	6.56	7	253	<2	33	5.71	<4	43	168	69	5.23	0.10	22	2.41	1462	<1	82	1049	15	0.54	<5	<5	<10	205	7319	11	183	<10	21	280
184624D	1408707	0.098	<1	6.56	8	258	<2	53	5.82	<4	43	171	71	5.29	0.13	22	2.48	1453	<1	83	1056	18	0.55	<5	<5	<10	210	6894	10	187	<10	21	288
184625	1408708	0.017	<1	6.05	4	185	<2	36	5.68	<4	40	163	62	5.67	0.06	10	2.41	1589	<1	77	1071	11	0.31	<5	<5	<10	168	5927	2	181	<10	21	122
184626	1408709	0.015	<1	6.52	2	192	<2	40	5.62	<4	41	167	65	6.47	0.13	11	2.34	1752	<1	80	1113	7	0.33	<5	<5	<10	194	7363	<2	187	<10	22	136
184627	1408710	0.014	<1	6.10	35	244	<2	21	5.90	<4	39	163	75	6.03	0.19	13	1.89	1801	<1	76	1020	7	0.39	<5	<5	<10	208	8240	18	173	<10	19	88
184628	1408711	0.033	<1	4.55	4	263	<2	41	4.07	<4	36	147	26	5.33	0.22	16	2.18	1532	<1	73	878	10	0.28	<5	<5	<10	140	6956	12	161	<10	17	90
184629	1408712	0.055	<1	4.79	2	190	<2	34	6.49	<4	25	97	50	7.62	0.18	9	2.57	2715	<1	53	578	9	0.90	6	<5	<10	126	4653	<2	114	<10	33	227
184630	1408713	0.289	<1	2.46	4	167	<2	51	2.00	<4	14	43	25	7.11	0.19	15	1.20	1818	<1	46	406	7	1.27	<5	<5	<10	73	3313	<2	40	<10	36	107
184631	1408714	0.030	<1	2.31	7	204	<2	26	2.01	<4	11	33	15	5.17	0.16	16	0.63	1291	<1	36	393	9	0.67	<5	<5	<10	83	3501	<2	7	<10	53	135
184632	1408715	0.008	<1	2.20	2	232	<2	36	1.93	<4	11	25	8	3.65	0.11	10	0.35	1027	<1	34	356	5	0.39	<5	<5	<10	122	3782	<2	6	<10	55	101
184633	1408716	0.011	<1	2.96	5	263	<2	40	2.12	<4	16	60	23	4.05	0.06	15	0.44	975	<1	41	644	4	0.43	<5	<5	<10	132	5329	<2	64	<10	40	85
184634	1408717	0.033	<1	3.06	<2	158	<2	20	2.42	<4	8	31	13	5.07	<0.01	13	0.56	1475	<1	33	404	4	0.47	<5	<5	<10	96	3481	<2	7	<10	66	109
184635D	1408717	0.013	<1	3.92	2	147	<2	37	2.39	<4	8	31	13	4.98	<0.01	11	0.63	1397	<1	34	440	3	0.44	<5	<5	<10	94	3259	<2	6	<10	89	101
184636	1408718	0.010	<1	4.77	<2	209	<2	44	1.95	<4	8	27	8	5.06	0.05	17	0.87	1296	<1	24	496	6	0.46	<5	<5	<10	90	3393	<2	6	<10	89	74
184637	1408719	0.010	<1	6.85	9	246	<2	36	3.78	<4	29	144	18	5.11	0.05	21	1.49	1294	<1	79	665	4	0.54	<5	5	<10	138	4606	<2	99	<10	42	105
184638	1408720	2.433	<1	4.50	4	461	<2	52	2.10	<4	16	58	27	3.48	0.23	4	1.24	676	<1	31	558	8	0.23	6	<5	<10	255	2875	<2	115	19	15	48
184639	1408721	0.013	<1	6.66	6	172	<2	22	5.50	<4	67	208	94	8.66	0.22	14	2.28	2116	<1	139	399	7	2.19	<5	<5	<10	149	3880	4	134	<10	15	130

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/03/2012
 Date Completed:
 Job #: 201242455
 Reference: TL 12 253
 Sample #: 219

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
184640	1408722	0.016	<1	<0.01	<2	21	2	6	0.58	8	56	44	87	9.11	<0.01	<1	3.13	2598	<1	203	662	16	1.43	<5	<5	<10	293	5553	<2	204	12	25	415
184641	1408723	0.019	<1	5.51	4	166	<2	32	5.36	<4	43	265	51	6.80	0.15	10	2.02	1800	<1	132	441	10	0.76	<5	<5	<10	195	4220	11	153	<10	13	92
184642	1408724	0.005	<1	5.07	<2	247	<2	41	5.11	<4	49	278	86	6.91	0.07	14	1.73	1823	<1	142	459	6	0.81	<5	<5	<10	207	4792	12	175	<10	12	94
184643	1408725	<0.005	<1	4.94	5	182	<2	37	5.39	<4	39	272	46	6.48	0.07	9	1.66	1793	<1	121	420	7	0.43	<5	<5	<10	216	4797	2	173	<10	12	89
184644	1408726	<0.005	<1	5.09	3	182	<2	39	5.71	<4	40	273	56	6.95	0.08	10	1.85	1780	<1	131	408	11	0.47	<5	<5	<10	211	4484	2	171	<10	14	97
184645	1408727	0.013	<1	4.63	<2	247	<2	61	6.07	<4	49	271	91	7.85	0.06	8	1.80	1920	<1	141	523	7	0.61	<5	<5	<10	201	5673	7	186	<10	14	120
184646D	1408727	0.008	<1	6.56	<2	240	<2	42	6.04	<4	49	267	89	7.72	0.05	9	1.92	1861	<1	140	550	8	0.61	<5	<5	<10	199	5406	<2	181	<10	17	117
184647	1408728	0.035	<1	6.40	8	318	<2	45	5.71	<4	46	197	29	6.54	<0.01	16	1.53	1456	<1	117	829	11	0.46	<5	<5	<10	237	6137	11	180	<10	13	114
184648	1408729	0.015	<1	6.33	8	398	<2	17	2.59	<4	32	191	18	4.63	0.24	19	1.48	890	<1	83	773	5	0.33	<5	<5	11	200	4509	6	144	<10	12	54
184649	1408730	<0.005	<1	5.96	<2	446	<2	36	1.80	<4	5	33	3	1.27	0.24	6	0.40	211	<1	33	264	11	0.35	<5	<5	<10	184	1345	2	26	<10	4	14
184650	1408731	0.022	<1	4.87	4	453	<2	34	1.52	<4	4	33	2	1.23	0.15	5	0.36	216	<1	45	245	12	0.53	<5	<5	<10	215	1140	<2	21	<10	4	29
184651	1408732	0.028	<1	6.21	11	461	<2	47	1.60	<4	4	32	3	1.15	0.22	7	0.37	223	<1	35	249	16	0.55	<5	<5	<10	251	1141	<2	21	<10	4	44
184652	1408733	0.014	<1	4.70	2	467	<2	40	1.56	<4	4	43	2	1.30	0.27	8	0.36	223	<1	46	256	10	0.57	<5	<5	<10	286	1234	<2	23	<10	3	27
184653	1408734	0.006	<1	4.76	<2	425	<2	29	1.55	<4	4	31	<1	1.26	0.08	8	0.37	198	<1	36	256	8	0.57	<5	<5	<10	298	1266	<2	22	<10	3	10
184654	1408735	0.056	<1	4.61	<2	515	<2	17	1.33	<4	4	35	<1	1.18	0.04	7	0.29	171	<1	40	238	9	0.50	<5	<5	<10	363	1292	<2	23	<10	3	12
184655	1408736	<0.005	<1	3.47	5	476	<2	44	1.67	<4	3	50	<1	0.94	<0.01	2	0.22	160	2	45	151	4	0.31	<5	<5	<10	306	1065	<2	18	<10	2	7
184656	1408737	<0.005	<1	4.72	<2	525	<2	27	1.32	<4	5	34	<1	1.20	<0.01	8	0.33	167	<1	36	228	9	0.25	<5	<5	<10	359	1308	<2	22	<10	3	21
184657R	1408737	<0.005	<1	4.69	3	568	<2	36	1.30	<4	4	34	<1	1.20	0.02	8	0.31	164	<1	40	215	7	0.25	<5	<5	<10	370	1325	<2	22	<10	2	21
184658	1408738	<0.005	<1	5.72	4	450	<2	19	1.42	<4	4	34	1	1.24	0.13	10	0.39	194	<1	37	257	4	0.54	<5	5	<10	327	1313	<2	22	<10	4	76
184659	1408739	<0.005	<1	6.29	8	553	<2	38	1.49	<4	5	42	1	1.34	<0.01	12	0.38	189	3	58	255	8	0.31	<5	<5	<10	366	1378	3	24	<10	4	32

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/03/2012
 Date Completed:
 Job #: 201242455
 Reference: TL 12 253
 Sample #: 219

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
184660	1408740	<0.005	<1	3.79	6	430	<2	24	2.25	<4	16	59	21	3.46	0.01	3	1.30	693	<1	30	574	6	0.19	<5	<5	<10	268	3023	<2	117	14	15	52
184661	1408741	0.007	<1	6.13	5	497	<2	31	1.23	<4	4	38	<1	1.30	<0.01	14	0.47	185	<1	41	262	7	0.28	5	<5	<10	260	1416	<2	25	<10	4	13
184662	1408742	<0.005	<1	5.33	<2	449	<2	38	1.80	<4	4	38	<1	1.33	0.25	11	0.48	185	<1	47	257	8	0.30	<5	<5	<10	278	1257	<2	23	<10	4	7
184663	1408743	<0.005	<1	6.34	<2	454	<2	29	1.62	<4	4	44	1	1.35	0.20	8	0.34	168	3	51	277	7	0.26	<5	<5	<10	462	1421	<2	24	<10	4	14
184664	1408744	<0.005	<1	6.17	7	652	<2	21	1.55	<4	4	42	<1	1.30	0.27	7	0.34	181	<1	53	277	9	0.22	<5	<5	<10	430	1370	<2	23	<10	4	16
184665	1408745	<0.005	<1	6.81	<2	527	<2	39	1.69	<4	4	34	<1	1.17	0.19	7	0.36	203	<1	36	256	9	0.46	<5	<5	<10	403	1369	<2	23	<10	4	18
184666	1408746	<0.005	<1	5.76	6	477	<2	42	1.62	<4	4	34	<1	1.19	0.22	6	0.38	217	<1	38	267	7	0.42	<5	<5	<10	377	1325	<2	22	<10	4	14
184667	1408747	<0.005	<1	6.25	4	425	<2	35	1.83	<4	4	38	<1	1.28	0.19	6	0.38	212	<1	48	255	7	0.46	<5	<5	<10	349	1323	<2	22	<10	4	19
184668D	1408747	<0.005	<1	4.95	3	384	<2	46	1.66	<4	4	32	<1	1.21	0.16	4	0.37	200	<1	39	244	7	0.41	<5	<5	<10	319	1247	<2	21	<10	4	18
184669	1408748	<0.005	<1	6.21	4	471	<2	30	1.67	<4	4	35	<1	1.21	0.20	6	0.34	175	<1	35	264	8	0.44	<5	<5	<10	359	1331	<2	22	<10	4	14
184670	1408749	0.006	<1	5.03	5	505	<2	16	1.59	<4	5	64	2	1.39	0.06	5	0.38	192	6	98	262	6	0.31	<5	<5	<10	366	1332	<2	24	<10	3	15
184671	1408750	<0.005	<1	6.23	7	629	<2	32	1.77	<4	4	50	1	1.30	<0.01	8	0.33	165	3	64	263	10	0.27	<5	<5	<10	411	1435	<2	24	<10	4	13
184672	1408751	0.006	<1	5.93	<2	499	<2	26	1.79	<4	4	49	1	1.29	0.26	5	0.33	156	3	61	269	10	0.29	<5	<5	<10	393	1366	<2	23	<10	4	15
184673	1408752	0.007	<1	4.53	5	480	<2	22	1.96	<4	4	53	2	1.49	0.18	5	0.48	287	3	78	242	6	0.38	<5	6	<10	367	1306	<2	24	<10	3	17
184674	1408753	<0.005	<1	5.56	3	604	<2	38	1.52	<4	4	57	2	1.47	0.26	7	0.37	169	5	83	270	7	0.27	<5	<5	<10	371	1385	2	25	<10	4	16
184675	1408754	<0.005	<1	5.94	2	611	<2	25	1.87	<4	4	66	2	1.46	0.19	7	0.40	198	5	92	266	6	0.31	<5	<5	<10	395	1439	<2	26	<10	4	16
184676	1408755	0.008	<1	5.59	2	690	<2	29	1.47	<4	4	66	2	1.58	0.27	6	0.34	162	6	91	267	6	0.29	<5	<5	<10	393	1410	<2	26	<10	4	18
184677	1408756	0.007	<1	5.22	<2	533	<2	43	1.50	<4	5	59	3	1.43	0.16	7	0.38	201	4	76	283	9	0.28	<5	<5	<10	369	1372	<2	24	<10	4	22
184678	1408757	<0.005	<1	5.43	6	590	<2	48	1.42	<4	4	61	6	1.49	0.21	9	0.37	181	6	87	260	5	0.36	<5	<5	<10	390	1346	<2	25	<10	4	12
184679D	1408757	<0.005	<1	4.90	<2	559	<2	31	1.32	<4	5	57	6	1.41	0.16	7	0.35	171	7	81	250	6	0.34	<5	<5	<10	375	1272	<2	23	<10	3	12

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/03/2012
 Date Completed:
 Job #: 201242455
 Reference: TL 12 253
 Sample #: 219

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
184680	1408758	<0.005	<1	4.50	4	474	<2	42	1.35	<4	4	61	6	1.41	0.10	7	0.35	215	5	91	253	6	0.24	<5	<5	<10	312	1275	<2	24	<10	3	15
184681	1408759	<0.005	<1	6.75	4	514	<2	36	1.34	<4	4	57	2	1.36	0.15	10	0.31	225	6	78	280	8	0.26	<5	<5	<10	405	1348	2	24	<10	4	13
184682	1408760	0.270	<1	0.10	434	>5000	<2	25	0.79	<4	7	29	30	3.01	0.01	<1	0.05	<100	9	14	<100	21	0.52	18	5	<10	115	974	8	16	44	7	11
184683	1408761	<0.005	<1	6.04	3	624	<2	34	1.42	<4	4	58	2	1.43	0.09	9	0.30	204	6	82	265	12	0.22	<5	<5	<10	407	1432	<2	25	<10	4	15
184684	1408762	0.012	<1	5.89	2	547	<2	22	1.46	<4	4	59	4	1.49	0.18	13	0.45	214	5	90	253	9	0.29	<5	<5	<10	297	1324	<2	25	<10	4	41
184685	1408763	0.065	<1	5.81	17	474	<2	47	3.23	<4	5	63	14	1.66	0.11	12	0.54	495	6	93	259	18	0.55	<5	5	<10	249	1252	<2	27	<10	4	57
184686	1408764	0.097	<1	6.09	12	565	<2	44	1.72	<4	5	61	13	1.62	0.24	14	0.67	380	5	84	272	10	0.58	<5	7	<10	225	1309	<2	25	<10	4	79
184687	1408765	0.008	<1	6.48	8	500	<2	31	2.04	<4	4	46	3	1.51	0.20	12	0.53	385	2	60	282	6	0.62	<5	7	<10	267	1332	2	27	<10	4	18
184688	1408766	0.013	<1	5.98	4	456	<2	32	1.71	<4	4	51	3	1.47	0.31	11	0.49	333	4	73	264	9	0.54	<5	<5	<10	245	1277	<2	25	<10	4	15
184689	1408767	<0.005	<1	5.52	8	595	<2	20	1.38	<4	4	52	4	1.37	0.08	10	0.34	155	3	73	259	8	0.23	<5	<5	<10	316	1310	<2	24	<10	4	19
184690D	1408767	0.007	<1	4.95	3	607	<2	44	1.39	<4	4	52	5	1.42	0.09	10	0.35	162	3	74	270	7	0.21	<5	<5	<10	319	1341	<2	24	<10	3	18
184691	1408768	<0.005	<1	6.01	2	473	<2	45	1.33	<4	4	55	2	1.31	0.08	10	0.32	167	5	73	262	8	0.24	<5	5	<10	298	1300	<2	23	<10	4	16
184692	1408769	0.006	<1	4.55	4	451	<2	46	1.29	<4	4	50	2	1.24	0.14	8	0.32	194	2	67	242	7	0.19	<5	6	<10	329	1180	<2	20	<10	3	23
184693	1408770	<0.005	<1	7.01	6	623	<2	53	1.56	<4	4	55	1	1.35	0.21	12	0.31	181	5	72	271	9	0.27	<5	<5	<10	370	1417	7	24	<10	5	19
184694	1408771	<0.005	<1	6.04	3	562	<2	37	1.49	<4	4	55	2	1.36	0.18	10	0.32	179	5	77	265	9	0.23	<5	<5	<10	364	1369	<2	24	<10	4	18
184695	1408772	0.005	<1	5.94	8	621	<2	27	1.54	<4	3	55	1	1.35	0.10	10	0.32	190	5	80	253	4	0.21	<5	<5	<10	326	1326	<2	23	<10	4	15
184696	1408773	0.018	<1	7.30	5	665	<2	37	1.70	<4	4	56	3	1.37	0.29	14	0.32	184	5	70	277	11	0.37	<5	<5	<10	326	1372	<2	24	<10	5	24
184697	1408774	0.053	<1	6.32	9	584	<2	34	1.74	<4	4	58	5	1.37	0.16	17	0.35	184	5	87	273	15	0.41	<5	<5	<10	296	1331	3	24	<10	4	41
184698	1408775	0.016	<1	6.56	6	580	<2	45	1.81	<4	5	59	4	1.40	0.04	17	0.37	223	5	79	262	13	0.46	<5	<5	<10	269	1336	<2	25	<10	4	27
184699	1408776	0.022	<1	6.03	7	540	<2	31	1.60	<4	4	54	4	1.39	0.06	15	0.40	220	4	82	251	14	0.36	<5	<5	<10	241	1332	<2	24	<10	4	24

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/24/2012
 Date Completed: 08/10/2012
 Job #: 201242807
 Reference: TL12254
 Sample #: 255

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
212168	1367139	<0.005	<1	5.82	7	460	<2	9	2.23	<4	7	28	3	1.54	0.07	21	0.64	322	<1	33	395	1	1.03	<5	<5	<10	294	1510	<2	30	<10	6	30
212169	1367140	1.966	<1	4.12	10	423	<2	10	2.25	<4	18	64	40	3.96	0.01	15	1.53	754	3	37	711	11	0.52	<5	<5	<10	272	2863	<2	124	23	17	61
212170	1367141	<0.005	<1	3.11	6	479	<2	6	1.61	<4	6	39	6	1.57	<0.01	13	0.55	267	1	54	405	6	0.60	<5	<5	<10	222	1524	<2	29	<10	5	35
212171	1367142	<0.005	<1	4.73	<2	518	<2	3	1.61	<4	7	35	6	1.53	0.12	19	0.69	263	2	45	410	6	0.71	<5	8	<10	262	1549	<2	29	<10	6	36
212172	1367143	<0.005	<1	4.17	2	445	<2	14	1.69	<4	8	33	2	1.46	0.09	16	0.59	287	<1	44	403	4	0.81	<5	<5	<10	278	1482	<2	27	<10	5	30
212173	1367144	<0.005	<1	4.59	4	446	<2	12	1.69	<4	7	38	2	1.49	0.05	16	0.54	227	1	51	399	7	0.64	<5	<5	<10	274	1505	<2	28	<10	5	37
212174	1367145	<0.005	<1	4.75	9	444	<2	11	1.72	<4	8	51	3	1.62	<0.01	18	0.57	268	5	76	406	8	0.76	<5	<5	<10	301	1549	<2	30	<10	5	34
212175	1367146	0.007	<1	4.92	13	5	2	22	2.21	11	43	112	7	17.06	<0.01	19	0.78	1699	43	195	436	25	>10.00	<5	<5	<10	293	1647	<2	36	<10	6	64
212176	1367147	0.009	<1	4.20	8	631	<2	11	1.50	<4	6	41	4	1.55	<0.01	18	0.59	213	4	65	417	7	0.56	<5	<5	<10	253	1518	<2	31	<10	5	40
212177	1367148	<0.005	<1	4.64	3	576	<2	12	2.19	<4	7	39	7	1.77	0.05	21	0.84	307	4	60	417	7	0.66	<5	<5	<10	292	1519	<2	30	<10	5	44
212178D	1367148	0.008	<1	4.43	3	546	2	7	2.16	<4	7	34	10	1.76	0.05	19	0.83	298	6	58	417	10	0.64	<5	<5	<10	314	1553	<2	29	<10	5	43
212179	1367149	<0.005	<1	2.92	3	486	<2	5	2.24	<4	7	30	4	1.88	<0.01	15	1.16	454	1	48	386	3	0.67	<5	<5	<10	305	1364	<2	28	<10	5	38
212180	1367150	<0.005	<1	6.20	6	563	<2	11	2.15	<4	8	54	5	1.79	0.08	23	0.97	369	7	83	411	10	0.93	<5	8	<10	300	1500	<2	31	<10	6	36
212181	1367151	0.005	<1	4.43	6	436	<2	6	1.85	<4	6	46	5	1.68	0.06	17	0.81	372	5	72	389	6	0.89	<5	<5	<10	268	1314	<2	29	<10	5	30
212182	1367152	0.025	<1	4.84	7	485	<2	14	1.78	<4	7	49	5	1.63	0.06	17	0.57	222	6	78	389	4	0.63	<5	<5	<10	247	1493	<2	30	<10	5	42
212183	1367153	<0.005	<1	4.42	8	435	<2	10	1.62	<4	7	45	6	1.58	0.06	15	0.55	219	4	70	419	7	0.63	<5	<5	<10	249	1477	<2	29	<10	5	47
212184	1367154	<0.005	<1	4.52	3	426	<2	13	1.55	<4	7	50	16	1.55	0.09	14	0.53	241	4	78	414	10	0.69	<5	<5	<10	268	1497	<2	29	<10	5	86
212185	1367155	<0.005	<1	4.64	6	426	<2	16	1.71	<4	7	40	4	1.59	0.06	15	0.59	256	3	61	396	7	0.69	<5	<5	<10	268	1473	<2	29	<10	5	37
212186	1367156	0.011	<1	4.56	6	372	<2	10	1.84	<4	7	38	6	1.59	0.01	14	0.56	261	2	62	421	7	0.76	<5	5	<10	288	1465	<2	30	<10	5	58
212187	1367157	0.012	<1	4.22	9	338	<2	9	1.69	<4	7	45	3	1.60	<0.01	13	0.54	276	4	72	402	9	0.71	<5	<5	<10	273	1509	<2	30	<10	5	37

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/24/2012
 Date Completed: 08/10/2012
 Job #: 201242807
 Reference: TL12254
 Sample #: 255

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
212188	1367158	0.006	<1	3.69	5	342	<2	8	1.63	<4	7	33	4	1.51	<0.01	12	0.54	261	<1	50	394	4	0.71	<5	<5	<10	250	1519	<2	28	<10	5	49
212189D	1367158	<0.005	<1	4.99	12	355	<2	10	1.81	<4	6	47	3	1.59	<0.01	14	0.56	269	5	73	398	6	0.80	<5	<5	<10	291	1551	<2	30	<10	5	51
212190	1367159	0.007	<1	3.79	5	353	<2	6	1.76	<4	7	27	7	1.52	<0.01	13	0.58	319	<1	64	398	4	0.91	<5	<5	<10	249	1509	<2	28	<10	5	51
212191	1367160	<0.005	<1	4.60	6	425	<2	9	2.45	<4	17	64	30	3.64	0.06	14	1.51	734	3	57	705	15	0.55	<5	<5	<10	302	3023	<2	122	23	17	61
212192	1367161	0.008	<1	4.68	11	415	<2	14	1.95	<4	8	47	5	1.52	0.02	14	0.59	307	4	89	409	6	0.81	<5	<5	<10	303	1545	<2	30	<10	5	43
212193	1367162	<0.005	<1	4.36	7	502	<2	11	1.57	<4	7	54	4	1.73	0.09	18	0.98	385	8	109	391	7	0.85	<5	<5	<10	297	1498	<2	30	<10	5	37
212194	1367163	<0.005	<1	5.17	6	479	<2	16	1.87	<4	8	30	4	1.62	0.06	18	0.87	317	2	63	397	11	0.96	<5	<5	<10	258	1476	<2	30	<10	5	39
212195	1367164	<0.005	<1	5.00	4	503	<2	11	1.67	<4	6	26	4	1.45	0.04	17	0.81	281	<1	61	377	4	0.85	<5	5	<10	254	1438	<2	28	<10	5	40
212196	1367165	<0.005	<1	5.90	2	641	<2	4	1.71	<4	6	32	3	1.47	0.06	20	0.70	254	3	68	384	8	0.91	<5	<5	<10	244	1523	<2	29	<10	6	34
212197	1367166	<0.005	<1	6.11	5	674	<2	12	1.83	<4	7	50	4	1.63	0.09	19	0.69	267	5	102	415	8	0.88	<5	<5	<10	259	1536	<2	31	<10	5	32
212198	1367167	<0.005	<1	4.90	8	427	<2	10	1.64	<4	7	32	3	1.58	0.06	16	0.67	323	1	72	407	8	0.93	<5	<5	<10	259	1489	<2	29	<10	5	30
212199	1367168	0.006	<1	4.57	4	347	<2	8	1.59	<4	7	28	4	1.49	<0.01	14	0.57	302	<1	59	410	9	0.89	<5	<5	<10	246	1509	<2	28	<10	5	30
212200D	1367168	<0.005	<1	4.88	6	347	<2	13	1.66	<4	7	31	4	1.52	0.05	15	0.58	306	<1	65	411	5	0.92	5	<5	<10	255	1496	<2	28	<10	5	31
212201	1367169	<0.005	<1	3.56	<2	367	<2	9	1.54	<4	6	31	8	1.50	0.05	11	0.60	318	<1	64	382	5	0.73	<5	<5	<10	240	1483	<2	27	<10	5	39
212202	1367170	0.009	<1	2.73	3	563	<2	13	1.24	<4	7	41	26	1.65	<0.01	12	0.75	360	3	82	399	6	0.65	<5	<5	<10	214	1374	<2	29	<10	4	31
212203	1367171	0.009	<1	5.42	<2	523	<2	9	1.72	<4	6	28	16	1.54	0.06	18	0.74	354	<1	53	406	10	0.93	<5	<5	<10	271	1470	<2	29	<10	5	27
212204	1367172	<0.005	<1	3.99	2	488	<2	17	1.77	<4	6	30	7	1.47	0.06	12	0.55	312	<1	59	389	8	0.76	<5	<5	<10	244	1466	<2	27	<10	5	33
212205	1367173	<0.005	<1	4.91	13	431	<2	8	2.00	<4	7	28	4	1.53	0.06	15	0.63	353	<1	56	401	9	0.88	<5	<5	<10	284	1495	<2	29	11	5	33
212206	1367174	<0.005	<1	1.73	<2	481	<2	10	1.19	<4	8	26	2	1.37	0.02	7	0.48	257	<1	56	388	3	0.57	<5	<5	<10	167	1393	<2	26	<10	4	34
212207	1367175	<0.005	<1	4.78	6	515	<2	4	1.77	<4	7	39	3	1.57	0.05	13	0.58	318	2	75	410	5	0.80	<5	<5	<10	236	1605	<2	30	<10	6	36

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/24/2012
 Date Completed: 08/10/2012
 Job #: 201242807
 Reference: TL12254
 Sample #: 255

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
212208	1367176	<0.005	<1	4.90	2	479	<2	11	1.97	<4	7	32	3	1.76	0.09	13	0.86	427	2	61	405	8	0.74	<5	6	<10	259	1438	<2	31	<10	5	35
212209	1367177	0.009	<1	5.69	5	434	<2	10	1.71	<4	6	60	4	1.71	0.04	15	0.65	339	8	107	388	5	0.99	<5	<5	<10	251	1390	<2	30	<10	5	22
212210	1367178	0.017	<1	4.70	12	449	<2	8	1.61	<4	6	35	7	1.71	0.02	15	0.91	415	2	75	384	11	0.88	<5	<5	<10	281	1433	<2	29	<10	5	26
212211D	1367178	0.016	<1	5.53	4	450	<2	15	1.75	<4	6	43	7	1.72	0.05	17	0.92	411	4	79	388	3	0.95	<5	<5	<10	305	1469	<2	29	<10	5	26
212212	1367179	0.007	<1	2.84	9	433	<2	12	1.20	<4	6	35	4	1.50	0.10	11	0.70	327	<1	66	365	8	0.63	<5	<5	<10	239	1364	<2	26	<10	4	20
212213	1367180	0.239	<1	<0.01	420	>5000	<2	3	0.74	<4	6	21	37	3.04	0.14	4	0.20	<100	12	29	100	19	0.94	16	<5	<10	95	636	<2	15	49	8	20
212214	1367181	0.010	<1	4.76	6	438	<2	11	2.05	<4	6	31	4	1.77	0.01	17	0.87	506	2	60	451	10	0.79	<5	5	<10	299	1569	<2	30	<10	6	25
212215	1367182	<0.005	<1	4.75	9	520	<2	7	1.50	<4	7	36	9	1.56	0.03	15	0.57	242	2	71	405	6	0.67	<5	<5	<10	298	1536	<2	29	<10	5	37
212216	1367183	<0.005	<1	5.32	<2	548	<2	6	1.75	<4	7	47	4	1.59	0.06	16	0.56	257	5	90	391	5	0.67	<5	12	<10	321	1528	<2	30	<10	5	36
212217	1367184	0.009	<1	5.52	8	477	<2	14	1.82	<4	7	34	4	1.68	0.08	18	0.78	359	3	66	431	9	0.92	<5	<5	<10	331	1514	<2	30	<10	6	35
212218	1367185	<0.005	<1	5.34	12	424	<2	13	1.91	<4	6	51	5	1.66	0.12	15	0.73	352	7	97	392	5	0.78	<5	<5	<10	308	1518	<2	30	<10	6	30
212219	1367186	<0.005	<1	5.61	2	465	<2	11	2.04	<4	6	43	5	1.51	0.04	15	0.72	396	5	83	398	6	0.80	<5	<5	<10	311	1459	<2	30	<10	6	32
212220	1367187	<0.005	<1	3.83	9	515	<2	5	1.57	<4	6	30	6	1.47	0.05	13	0.78	359	<1	56	375	5	0.65	<5	<5	<10	282	1467	<2	27	<10	5	28
212221	1367188	0.008	<1	5.62	2	473	<2	10	2.06	<4	7	40	3	1.67	0.06	17	0.65	286	2	73	397	6	0.66	<5	<5	<10	313	1548	<2	29	<10	6	45
212222D	1367188	<0.005	<1	5.19	2	469	<2	5	2.01	<4	7	36	3	1.65	0.16	15	0.64	284	2	70	391	9	0.62	<5	5	<10	308	1540	<2	29	<10	5	44
212223	1367189	0.035	<1	5.86	3	517	<2	9	1.81	<4	9	44	11	1.62	0.15	15	0.58	225	4	78	422	11	0.63	<5	<5	<10	340	1602	<2	31	<10	6	45
212224	1367190	<0.005	<1	4.81	<2	492	<2	12	1.65	<4	8	43	6	1.54	0.07	14	0.59	248	4	78	394	9	0.63	<5	<5	<10	297	1485	<2	29	<10	5	50
212225	1367191	0.008	<1	4.80	5	427	<2	9	1.84	<4	7	36	5	1.63	0.04	14	0.84	367	2	69	418	6	0.74	<5	<5	<10	335	1419	<2	29	<10	5	39
212226	1367192	0.009	<1	4.31	5	502	<2	6	1.46	<4	8	45	3	1.62	<0.01	12	0.68	324	5	71	420	3	0.68	<5	<5	<10	258	1425	<2	31	<10	5	34
212227	1367193	0.011	<1	5.01	5	493	<2	9	1.46	<4	6	34	2	1.53	<0.01	14	0.76	310	1	52	407	8	0.83	<5	5	<10	256	1379	<2	29	<10	6	31

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/24/2012
 Date Completed: 08/10/2012
 Job #: 201242807
 Reference: TL12254
 Sample #: 255

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
212228	1367194	0.007	<1	3.24	4	495	<2	6	1.41	<4	7	52	2	1.74	<0.01	9	0.80	379	6	85	389	5	0.67	<5	<5	<10	212	1324	<2	30	<10	4	36
212229	1367195	0.029	<1	5.63	5	535	<2	8	1.93	<4	6	39	2	1.53	<0.01	14	0.65	282	3	59	403	5	0.72	<5	<5	<10	245	1511	<2	30	<10	6	33
212230	1367196	0.048	<1	4.85	8	555	2	6	2.53	<4	8	33	3	2.21	<0.01	19	1.52	670	5	54	429	5	1.00	<5	<5	<10	296	1496	<2	33	<10	5	46
212231	1367197	0.040	<1	5.51	7	489	<2	9	1.84	<4	8	25	2	1.67	<0.01	18	1.08	407	<1	38	406	6	0.95	<5	<5	<10	256	1542	<2	30	<10	5	35
212232	1367198	0.006	<1	5.32	11	461	<2	7	1.75	<4	6	29	2	1.48	0.07	15	0.89	299	<1	47	444	7	0.73	<5	<5	<10	212	1440	<2	28	<10	6	33
212233R	1367198	0.010	<1	4.70	6	497	<2	16	1.51	<4	6	36	2	1.46	0.12	14	0.70	277	1	56	396	7	0.72	<5	<5	<10	198	1431	<2	28	<10	5	42
212234	1367199	0.019	<1	5.58	5	512	<2	8	1.65	<4	7	28	1	1.50	0.08	18	1.00	358	2	45	401	10	0.78	<5	<5	<10	251	1534	<2	29	<10	5	33
212235	1367200	<0.005	<1	4.68	9	424	<2	20	2.36	<4	17	61	27	3.48	0.11	14	1.46	699	3	37	675	4	0.59	<5	<5	<10	295	2966	<2	117	20	17	53
212236	1367201	0.013	<1	5.05	5	449	<2	7	1.70	<4	6	32	2	1.53	0.03	15	0.92	310	2	47	449	2	0.74	<5	<5	<10	203	1428	<2	28	<10	6	36
212237	1367202	0.007	<1	4.07	2	451	<2	5	1.47	<4	6	42	2	1.53	0.04	13	0.76	320	4	68	390	3	0.63	<5	12	<10	230	1319	<2	28	<10	5	40
212238	1367203	0.018	<1	5.57	9	424	<2	8	1.72	<4	7	41	2	1.60	<0.01	17	0.86	294	4	65	396	5	0.86	<5	<5	<10	260	1411	<2	29	<10	6	35
212239	1367204	0.008	<1	4.31	4	490	<2	11	1.36	<4	7	49	2	1.58	<0.01	17	0.85	296	6	78	391	5	0.71	<5	<5	<10	229	1406	<2	29	<10	5	38
212240	1367205	0.014	<1	5.51	<2	537	<2	12	1.45	<4	7	55	3	1.68	<0.01	17	0.73	258	8	93	415	10	0.79	<5	<5	<10	229	1526	<2	31	<10	6	37
212241	1367206	0.010	<1	5.44	7	546	<2	9	1.41	<4	8	60	3	1.68	0.04	16	0.70	252	10	102	411	4	0.75	<5	8	<10	231	1496	<2	31	<10	6	38
212242	1367207	0.009	<1	5.15	13	441	<2	10	1.44	<4	7	36	3	1.56	0.01	16	0.87	299	4	62	391	9	0.74	<5	<5	<10	216	1515	<2	28	<10	5	42
212243	1367208	0.019	<1	4.58	7	435	<2	7	1.53	<4	9	59	5	1.76	0.05	15	0.81	328	10	102	387	2	0.81	<5	<5	<10	263	1349	<2	31	<10	5	39
212244D	1367208	0.016	<1	5.58	11	446	<2	7	1.69	<4	8	56	5	1.76	0.10	17	0.84	330	9	98	390	10	0.88	<5	<5	<10	292	1418	<2	31	<10	5	42
212245	1367209	0.007	<1	5.34	6	437	<2	13	1.67	<4	7	32	2	1.53	0.06	15	0.84	331	2	55	429	9	0.73	<5	<5	<10	245	1517	<2	30	<10	6	48
212246	1367210	0.014	<1	5.12	5	499	2	10	1.62	<4	8	44	6	1.61	0.12	16	1.01	413	7	80	380	8	0.77	<5	<5	<10	249	1530	<2	29	<10	5	148
212247	1367211	0.030	<1	4.35	11	453	<2	12	1.71	<4	8	33	4	1.64	0.08	13	0.95	454	2	52	407	4	0.83	<5	<5	<10	236	1487	<2	29	<10	5	39

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/24/2012
 Date Completed: 08/10/2012
 Job #: 201242807
 Reference: TL12254
 Sample #: 255

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
212248	1367212	0.027	<1	4.88	7	486	<2	12	1.95	<4	6	59	6	1.80	0.13	12	0.88	426	9	99	404	7	0.82	<5	<5	<10	225	1404	<2	30	12	5	39
212249	1367213	<0.005	<1	3.80	<2	447	<2	5	1.60	<4	6	37	3	1.51	0.11	10	0.66	285	2	58	408	9	0.64	<5	<5	<10	178	1423	<2	26	<10	5	37
212250	1367214	0.009	<1	5.29	3	541	<2	11	1.58	<4	7	50	4	1.59	0.08	16	0.87	340	4	59	391	10	0.84	<5	<5	<10	295	1471	<2	29	<10	5	38
212251	1367215	0.035	<1	5.36	5	494	<2	9	1.26	<4	6	39	4	1.49	0.05	17	0.73	302	3	63	404	<1	0.94	<5	<5	<10	273	1373	<2	28	<10	5	35
212252	1367216	0.007	<1	5.01	4	520	<2	9	1.65	<4	6	40	3	1.41	0.11	12	0.62	288	1	56	379	4	0.71	<5	<5	<10	233	1438	<2	29	<10	5	30
212253	1367217	<0.005	<1	5.66	<2	516	<2	13	1.72	<4	6	36	2	1.46	0.14	14	0.59	314	2	49	396	4	0.80	<5	<5	<10	306	1497	<2	29	<10	5	28
212254	1367218	<0.005	<1	4.76	6	510	<2	6	1.49	<4	6	49	2	1.53	0.06	13	0.58	277	3	75	378	7	0.65	<5	<5	<10	314	1466	<2	29	<10	5	35
212255D	1367218	<0.005	<1	4.44	2	528	<2	10	1.52	<4	7	50	4	1.61	0.07	12	0.58	292	4	81	408	7	0.60	<5	10	<10	322	1534	<2	30	<10	5	57
212256	1367219	3.038	<1	4.38	7	545	<2	8	1.29	<4	7	46	3	1.51	0.15	12	0.57	244	3	77	403	5	0.69	<5	<5	<10	272	1434	<2	29	<10	5	42
212257	1367220	<0.005	63	2.94	34	463	<2	8	1.22	21	15	40	62	3.33	0.14	10	0.91	528	5	46	612	666	0.84	58	5	258	242	1932	<2	92	58	13	1897
212258	1367221	<0.005	<1	4.85	4	562	<2	7	1.45	<4	7	44	3	1.61	0.06	11	0.70	301	4	72	407	10	0.86	<5	<5	<10	335	1410	<2	31	<10	5	39
212259	1367222	0.005	<1	4.34	6	458	<2	4	1.78	<4	8	43	3	1.59	0.07	9	0.66	335	3	73	388	5	0.80	<5	<5	<10	251	1544	<2	28	<10	5	34
212260	1367223	<0.005	<1	3.92	6	419	<2	11	1.52	<4	6	46	3	1.43	0.05	9	0.55	257	2	70	381	3	0.64	<5	<5	<10	196	1504	<2	27	<10	5	40
212261	1367224	<0.005	<1	5.50	5	452	<2	11	1.73	<4	5	40	3	1.53	0.09	14	0.67	288	3	70	428	8	0.83	<5	<5	<10	222	1571	<2	29	<10	6	46
212262	1367225	<0.005	<1	5.70	<2	422	<2	12	2.00	<4	6	53	3	1.61	0.16	13	0.68	348	6	85	398	4	0.90	<5	<5	<10	248	1578	<2	30	<10	6	34
212263	1367226	<0.005	<1	4.75	3	313	<2	12	1.56	<4	7	33	2	1.42	0.13	12	0.71	371	<1	47	385	13	0.79	<5	<5	<10	211	1559	<2	28	<10	5	35
212264	1367227	0.007	<1	5.35	5	336	<2	10	1.77	<4	7	41	2	1.53	0.09	13	0.76	359	3	70	410	5	0.90	<5	5	<10	218	1572	<2	29	<10	6	33
212265	1367228	<0.005	<1	3.65	2	388	<2	14	1.28	<4	7	37	2	1.54	0.09	8	0.63	341	1	63	407	2	0.77	<5	<5	<10	184	1473	<2	28	<10	5	33
212266D	1367228	<0.005	<1	3.49	2	378	<2	16	1.25	<4	7	36	2	1.50	0.14	8	0.61	331	1	63	396	4	0.75	<5	<5	<10	182	1449	<2	27	<10	4	30
212267	1367229	<0.005	<1	5.25	5	427	<2	14	1.56	<4	6	45	3	1.66	0.09	14	0.87	422	3	67	402	9	0.86	<5	<5	<10	229	1470	<2	30	<10	5	38

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/24/2012
 Date Completed: 08/10/2012
 Job #: 201242807
 Reference: TL12254
 Sample #: 255

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
212268	1367230	0.007	<1	4.47	9	421	2	10	1.40	<4	6	31	3	1.63	0.08	14	0.94	433	2	61	402	8	0.83	<5	<5	<10	201	1532	<2	29	<10	5	45
212269	1367231	0.009	<1	5.99	4	572	<2	8	2.06	<4	9	34	4	1.95	0.12	15	1.17	582	4	69	515	11	1.00	<5	<5	<10	264	1584	<2	34	<10	6	39
212270	1367232	0.005	<1	6.82	8	620	<2	13	2.38	<4	9	49	6	2.27	0.13	19	1.23	640	9	84	756	10	1.17	<5	<5	<10	259	1950	<2	43	<10	8	35
212271	1367233	<0.005	<1	4.04	8	459	<2	9	1.65	<4	7	30	3	1.74	0.12	13	1.14	533	2	59	399	10	0.83	<5	<5	<10	183	1415	<2	29	<10	5	35
212272	1367234	0.019	<1	5.08	6	461	<2	9	1.62	<4	7	25	2	1.54	0.07	14	1.03	462	2	52	382	7	0.83	<5	<5	<10	182	1497	<2	29	<10	5	31
212273	1367235	0.016	<1	6.06	8	521	<2	6	2.38	<4	6	29	2	1.76	0.24	19	1.38	614	2	55	395	5	0.84	<5	<5	<10	228	1502	<2	28	<10	6	31
212274	1367236	<0.005	<1	5.77	10	466	<2	7	1.98	<4	6	38	3	1.69	0.07	19	1.22	523	4	68	399	6	0.88	<5	<5	<10	209	1564	<2	30	<10	6	34
212275	1367237	<0.005	<1	5.05	3	465	<2	5	1.35	<4	7	48	3	1.48	0.09	18	0.87	325	3	70	387	10	0.81	<5	<5	<10	202	1506	<2	29	<10	5	42
212276	1367238	<0.005	<1	5.32	5	459	2	4	3.56	<4	6	44	4	2.22	0.15	21	1.82	782	7	79	372	4	0.78	<5	<5	<10	306	1387	<2	30	<10	6	52
212277D	1367238	<0.005	<1	5.34	3	489	2	14	3.63	<4	6	40	4	2.21	0.17	19	1.82	783	5	73	371	8	0.74	<5	8	<10	317	1408	<2	30	<10	6	50
212278	1367239	<0.005	<1	4.91	4	535	2	10	1.54	<4	7	36	3	1.47	0.12	17	0.87	345	3	59	412	5	0.83	<5	<5	<10	306	1331	<2	28	<10	5	47
212279	1367240	<0.005	<1	1.75	<2	286	<2	11	1.92	<4	15	57	26	3.31	0.08	8	1.34	655	1	48	636	7	0.39	<5	<5	<10	216	2467	<2	109	16	15	51
212280	1367241	<0.005	<1	4.37	4	479	<2	6	1.40	<4	6	29	7	1.50	0.17	17	0.82	368	<1	50	414	8	0.84	<5	8	<10	283	1336	<2	29	<10	5	49
212281	1367242	0.006	<1	2.52	5	426	<2	10	1.11	<4	8	33	7	1.56	0.09	10	0.64	308	<1	44	395	5	0.66	<5	<5	<10	187	1412	<2	28	<10	4	43
212282	1367243	0.006	<1	5.18	3	488	<2	7	1.64	<4	9	31	8	1.58	0.03	16	0.64	276	1	60	419	10	0.90	<5	<5	<10	250	1606	<2	30	<10	6	38
212283	1367244	<0.005	<1	1.90	<2	318	<2	11	0.96	<4	5	23	6	1.19	<0.01	7	0.47	224	<1	42	319	5	0.52	<5	<5	<10	149	1138	<2	22	<10	4	36
212284	1367245	0.013	<1	5.18	11	500	<2	14	1.57	<4	8	36	4	1.73	0.12	18	0.97	407	2	52	408	8	0.95	<5	<5	<10	254	1526	<2	30	<10	5	47
212285	1367246	0.008	<1	5.37	5	480	<2	13	1.64	<4	7	34	4	1.69	0.14	19	0.98	411	3	61	392	6	0.92	<5	<5	<10	258	1522	<2	29	<10	5	43
212286	1367247	0.006	<1	4.82	3	464	<2	11	1.54	<4	7	29	3	1.50	0.20	17	0.69	279	<1	53	399	4	0.91	<5	<5	<10	227	1530	<2	28	<10	6	41
212287	1367248	<0.005	<1	2.96	<2	528	<2	5	1.22	<4	6	33	3	1.42	0.12	14	0.59	243	<1	61	368	3	0.63	<5	5	<10	249	1432	<2	27	<10	4	37

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/24/2012
 Date Completed: 08/10/2012
 Job #: 201242807
 Reference: TL12254
 Sample #: 255

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
212288D	1367248	0.009	<1	4.82	3	581	<2	5	1.46	<4	7	33	3	1.46	0.09	19	0.65	249	<1	63	389	8	0.83	<5	<5	<10	291	1496	<2	28	<10	5	38
212289	1367249	<0.005	<1	2.02	6	497	<2	8	1.11	<4	7	31	4	1.45	0.13	12	0.70	277	<1	64	350	6	0.54	<5	<5	<10	237	1444	<2	27	<10	4	35
212290	1367250	0.006	<1	4.73	8	443	<2	8	1.67	<4	7	41	4	1.59	0.17	17	0.67	292	3	73	405	6	0.87	5	<5	<10	246	1562	<2	29	<10	6	30
212291	1367251	0.023	<1	4.76	5	404	<2	13	1.71	<4	8	31	2	1.54	0.18	17	0.65	285	2	59	408	5	0.89	<5	<5	<10	256	1639	<2	29	<10	6	29
212292	1367252	<0.005	<1	3.89	6	438	<2	10	1.56	<4	7	35	3	1.53	0.13	14	0.60	289	1	64	409	11	0.77	<5	<5	<10	255	1600	<2	29	<10	5	28
212293	1367253	<0.005	<1	4.23	<2	480	<2	6	1.62	<4	6	31	2	1.44	0.17	16	0.58	250	<1	50	393	5	0.77	<5	<5	<10	278	1586	<2	28	<10	5	26
212294	1367254	0.020	<1	4.98	<2	458	<2	12	1.77	<4	6	38	6	1.55	0.17	19	0.76	362	3	67	385	7	0.89	<5	<5	<10	287	1535	<2	29	<10	5	29
212295	1367255	0.010	<1	2.59	8	469	<2	9	1.30	<4	7	29	3	1.49	0.14	14	0.54	224	<1	51	388	4	0.65	<5	<5	<10	190	1532	<2	29	<10	5	37
212296	1367256	<0.005	<1	4.38	4	483	<2	10	1.40	<4	7	29	5	1.49	0.16	19	0.56	228	<1	50	394	3	0.71	<5	<5	<10	266	1603	<2	28	<10	5	47
212297	1367257	0.010	<1	5.81	6	454	2	7	1.62	<4	7	33	4	1.52	0.20	23	0.65	281	2	56	396	7	0.93	<5	10	<10	295	1609	<2	30	<10	6	45
212298	1367258	<0.005	<1	4.94	4	375	<2	5	1.59	<4	7	31	7	1.52	0.13	20	0.65	322	1	50	394	5	0.92	<5	<5	<10	274	1609	<2	29	<10	6	32
212299R	1367258	0.007	<1	5.45	<2	397	<2	5	1.70	<4	8	47	7	1.65	0.18	22	0.67	339	5	81	404	8	0.94	<5	<5	<10	293	1658	<2	31	<10	6	30
212300	1367259	<0.005	<1	5.20	2	418	<2	3	1.70	<4	7	39	7	1.61	0.18	22	0.63	300	3	71	399	13	0.93	5	<5	<10	270	1638	<2	30	<10	6	33
212301	1367260	1.979	<1	4.69	3	440	<2	13	2.32	<4	18	64	39	3.96	0.16	16	1.52	760	4	61	718	13	0.58	<5	<5	<10	295	2975	<2	125	26	17	64
212302	1367261	0.018	<1	4.99	<2	482	<2	13	1.77	<4	8	32	14	1.66	0.11	21	0.63	386	1	61	422	8	0.93	<5	<5	<10	288	1734	<2	31	<10	6	39
212303	1367262	0.013	<1	3.34	<2	436	<2	10	1.55	<4	8	40	14	1.66	0.16	17	0.53	360	2	77	402	4	0.73	<5	<5	<10	258	1637	<2	30	<10	5	36
212304	1367263	0.009	<1	4.73	5	485	<2	13	1.52	<4	8	33	8	1.53	0.21	22	0.57	320	<1	60	399	9	0.74	<5	<5	<10	267	1627	<2	29	<10	6	34
212305	1367264	0.012	<1	3.90	<2	419	<2	6	1.42	<4	6	32	5	1.50	0.19	24	0.60	370	<1	58	396	6	0.87	<5	<5	<10	184	1571	<2	28	<10	5	27
212306	1367265	0.014	<1	5.07	8	405	<2	4	1.52	<4	8	32	3	1.48	0.30	23	0.70	376	<1	55	401	6	1.07	<5	<5	<10	257	1549	<2	28	<10	6	25
212307	1367266	0.008	<1	4.91	5	419	2	10	1.62	<4	8	46	5	1.62	0.18	24	0.58	343	3	82	409	3	0.86	<5	<5	<10	252	1659	<2	30	<10	6	33

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012


Final Certificate

Treasury Metals Inc
Exchange Tower 130 King St Suite 3680
Toronto, On, CAN
M5X 1B1
Ph#: (416) 599-4133
Fax#: (416) 599-4959
Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/24/2012
Date Completed: 08/10/2012
Job #: 201242807
Reference: TL12254
Sample #: 255

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
212308	1367267	<0.005	<1	4.90	6	454	<2	13	1.70	<4	6	63	6	1.70	0.17	23	0.56	330	6	99	426	6	0.80	6	<5	<10	243	1674	<2	31	<10	6	39
212309	1367268	0.008	<1	6.03	<2	450	<2	7	1.73	<4	9	36	6	1.57	0.27	29	0.64	380	2	76	413	3	1.02	5	<5	<10	236	1661	<2	30	<10	6	70
212310D	1367268	0.010	<1	4.67	3	430	<2	12	1.57	<4	8	37	5	1.56	0.22	25	0.61	380	1	61	409	4	0.90	<5	<5	<10	210	1636	<2	29	<10	6	38
212311	1367269	<0.005	<1	5.41	3	485	<2	8	1.58	<4	8	52	7	1.68	0.28	26	0.66	384	7	102	423	4	0.85	<5	<5	<10	202	1634	<2	31	<10	6	31
212312	1367270	0.006	<1	5.84	<2	587	2	2	2.12	<4	8	35	12	1.77	0.24	31	1.17	564	3	70	425	13	0.81	<5	<5	<10	242	1592	<2	30	<10	6	32
212313	1367271	0.042	<1	4.37	<2	84	3	10	2.10	10	117	67	221	13.42	0.14	29	1.27	1631	31	156	343	30	9.74	<5	<5	<10	198	1550	<2	37	<10	10	245
212314	1367272	0.007	<1	4.77	2	690	2	7	2.16	<4	7	44	27	1.86	0.34	30	0.72	702	3	87	401	14	0.91	<5	5	<10	367	1717	<2	37	<10	8	70
212315	1367273	0.007	<1	5.69	6	471	<2	11	2.76	<4	11	98	15	2.22	0.23	42	1.28	768	8	124	473	12	0.99	<5	7	<10	495	2017	<2	49	<10	8	37
212316	1367274	<0.005	<1	5.27	<2	379	<2	13	1.43	<4	9	52	16	1.97	0.24	32	0.91	596	6	89	386	7	1.05	<5	7	<10	221	1576	<2	41	<10	6	33
212317	1367275	0.118	<1	5.26	5	348	<2	16	2.01	<4	13	46	38	3.85	0.23	26	0.92	705	10	90	402	16	2.38	<5	<5	<10	229	1680	<2	32	<10	7	199
212318	1367276	0.005	<1	5.72	6	554	<2	13	1.84	<4	7	43	6	1.86	0.26	37	1.05	529	4	89	415	11	0.74	<5	6	<10	217	1714	<2	34	<10	7	52
212319	1367277	0.022	2	5.13	3	319	2	17	5.60	8	54	68	103	10.59	0.36	44	2.69	2015	<1	111	982	13	1.54	<5	5	<10	330	8474	<2	333	<10	42	151
212320	1367278	0.044	3	4.27	<2	60	2	21	4.59	7	75	66	179	10.38	0.22	44	2.40	1758	<1	122	969	17	2.77	<5	<5	<10	209	6724	<2	349	13	41	145
212321D	1367278	0.039	<1	4.78	<2	65	2	17	4.69	7	75	62	179	10.42	0.21	47	2.45	1759	<1	114	969	13	2.88	<5	<5	<10	214	6664	<2	354	15	42	132
212322	1367279	0.027	<1	4.87	<2	42	2	20	4.97	8	54	35	116	10.93	0.22	39	2.36	1585	<1	78	1128	13	2.05	<5	<5	<10	201	6338	<2	382	16	47	146
212323	1367280	<0.005	1	4.37	6	419	<2	<1	2.15	4	14	50	28	3.20	<0.01	10	1.39	629	<1	30	543	9	0.82	<5	<5	<10	287	2999	<2	108	24	17	77
212324	1367281	0.032	2	4.81	<2	34	2	17	4.31	6	53	37	116	9.90	0.21	34	2.12	1601	<1	87	1223	14	2.03	<5	5	<10	206	6562	<2	370	111	48	134
212325	1367282	0.045	<1	>10.00	4	1204	2	8	>10.00	7	64	132	163	10.64	1.45	62	2.82	2254	<1	87	972	11	2.66	<5	<5	<10	331	10017	<2	359	<10	38	132
212326	1367283	0.020	<1	5.52	<2	109	2	12	5.32	6	57	68	141	9.68	0.22	39	2.23	1804	<1	90	951	10	1.57	<5	<5	<10	298	8107	<2	362	<10	40	121
212327	1367284	0.014	2	5.24	<2	60	2	16	5.80	8	54	80	92	10.80	0.22	38	2.35	1763	<1	116	1060	16	1.09	<5	<5	<10	255	6578	<2	297	<10	45	132

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/24/2012
 Date Completed: 08/10/2012
 Job #: 201242807
 Reference: TL12254
 Sample #: 255

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
212328	1367285	<0.005	<1	5.30	2	142	2	17	6.23	7	68	86	173	10.54	0.22	46	2.54	1757	<1	120	885	11	1.54	<5	8	<10	352	7381	5	327	<10	37	124
212329	1367286	0.008	<1	5.11	5	159	2	13	6.07	7	65	81	153	10.44	0.17	48	2.55	1756	<1	127	904	15	1.41	<5	<5	<10	351	7234	2	328	12	37	124
212330	1367287	<0.005	<1	5.41	<2	83	2	18	5.76	6	57	149	104	9.39	0.22	49	2.99	1728	<1	166	931	9	1.10	<5	<5	<10	279	6052	<2	302	13	34	122
212331	1367288	0.072	<1	5.25	<2	54	2	22	5.68	9	63	50	132	12.66	0.26	45	2.73	1835	6	109	861	15	2.63	<5	<5	<10	247	6208	11	342	<10	37	147
212332D	1367288	0.064	<1	4.91	<2	51	2	17	5.54	9	62	50	130	12.36	0.22	43	2.66	1800	5	112	830	19	2.57	<5	<5	<10	242	6079	<2	334	<10	36	142
212333	1367289	<0.005	<1	4.06	<2	76	2	10	5.07	7	50	44	108	10.70	0.14	47	2.43	2223	<1	84	843	11	1.34	<5	<5	<10	219	5764	<2	308	18	39	127
212334	1367290	<0.005	<1	4.51	<2	121	2	16	5.33	8	58	45	128	10.93	0.20	62	2.69	2222	<1	76	1010	14	1.21	<5	<5	<10	257	7988	<2	355	<10	42	135
212335	1367291	<0.005	<1	4.29	3	79	2	23	5.54	7	60	49	171	10.55	0.27	59	2.65	2117	<1	89	976	15	1.98	5	7	<10	300	8908	<2	347	10	39	135
212336	1367292	0.041	3	4.18	<2	45	3	20	3.36	10	101	43	284	14.02	0.10	88	2.58	2042	3	101	838	11	4.41	<5	<5	<10	170	5162	<2	285	13	42	157
212337	1367293	0.018	<1	4.89	<2	81	2	15	5.14	11	86	50	237	15.02	0.14	80	2.91	2982	5	108	889	12	4.50	<5	<5	<10	217	6562	<2	334	<10	42	151
212338	1367294	<0.005	<1	3.69	<2	66	2	17	4.91	8	56	44	115	11.05	0.19	58	2.53	2079	<1	81	903	10	1.28	<5	<5	<10	196	5624	4	341	<10	39	134
212339	1367295	<0.005	2	5.31	2	64	2	20	6.08	8	56	65	115	11.24	0.16	49	2.70	1695	<1	95	912	13	1.19	<5	<5	<10	280	7370	<2	350	<10	41	130
212340	1367296	0.010	<1	5.40	<2	90	2	22	5.21	7	58	76	134	9.48	0.19	54	2.23	1653	<1	93	932	12	1.14	<5	<5	<10	216	6605	<2	348	<10	41	134
212341	1367297	<0.005	<1	5.44	<2	130	2	18	5.24	7	58	76	121	9.58	0.28	55	2.25	1687	<1	93	972	8	1.10	<5	<5	<10	248	6996	<2	353	<10	42	135
212342	1367298	<0.005	<1	4.33	3	99	<2	21	5.85	7	60	87	166	10.28	0.25	47	2.38	1893	<1	114	855	9	1.83	<5	7	<10	343	7233	<2	318	14	37	177
212343D	1367298	<0.005	2	4.85	<2	104	2	19	6.02	7	63	79	169	10.52	0.16	50	2.43	1940	<1	109	879	14	1.92	<5	<5	<10	353	7682	<2	325	10	38	179
212344	1367299	<0.005	<1	2.70	<2	36	<2	15	5.61	6	53	82	133	9.35	0.16	36	2.36	1676	<1	92	872	7	0.70	5	<5	<10	196	5896	<2	314	<10	36	118
212345	1367300	0.234	<1	<0.01	432	>5000	<2	14	0.79	<4	6	25	37	3.06	0.20	6	0.21	<100	<1	33	105	23	1.00	16	<5	<10	113	671	<2	16	52	8	17
212346	1367301	0.006	<1	4.24	4	144	2	16	6.17	7	55	94	146	10.43	0.20	57	3.11	1850	<1	102	923	15	1.02	<5	<5	<10	240	6826	<2	326	<10	38	126
212347	1367302	0.018	3	4.64	<2	133	2	19	5.93	8	54	80	153	11.07	0.20	55	2.88	1533	<1	77	854	7	1.10	<5	<5	<10	270	6164	3	329	<10	38	125

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/24/2012
 Date Completed: 08/10/2012
 Job #: 201242807
 Reference: TL12254
 Sample #: 255

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
212348	1367303	0.010	<1	4.49	<2	37	2	16	6.37	8	53	82	135	11.13	0.16	56	2.78	1422	<1	82	880	18	0.97	<5	<5	<10	266	6656	<2	337	<10	39	115
212349	1367304	<0.005	<1	4.56	4	92	<2	17	5.45	7	53	75	126	9.85	0.13	54	2.14	1727	<1	82	912	8	1.21	<5	<5	<10	233	6005	<2	338	<10	39	125
212350	1367305	0.007	<1	5.32	<2	67	2	13	5.78	7	57	75	151	10.71	0.15	56	2.42	1825	<1	89	1031	13	1.34	<5	8	<10	233	6722	<2	350	<10	41	138
212351	1367306	<0.005	1	5.19	7	68	2	15	5.99	8	54	77	137	10.74	0.26	52	2.50	1632	<1	90	979	9	1.12	<5	<5	<10	252	6471	<2	329	<10	42	135
212352	1367307	0.008	1	3.20	<2	165	2	16	5.18	7	54	90	152	10.33	0.22	53	2.41	1602	<1	97	884	11	0.78	<5	<5	<10	188	4891	<2	302	<10	36	124
212353	1367308	0.015	<1	4.35	<2	192	3	14	6.26	7	51	78	107	9.31	0.27	101	3.26	1789	<1	101	790	17	1.05	<5	<5	<10	219	6586	<2	300	<10	33	106
212354D	1367308	0.011	<1	4.54	3	200	2	12	6.47	7	52	80	111	9.65	0.24	107	3.36	1852	<1	91	824	11	1.07	<5	9	<10	221	6780	8	309	15	34	112
212355	1367309	0.006	<1	4.54	<2	69	<2	16	5.89	6	55	89	119	9.79	0.27	46	2.46	1711	<1	108	864	9	0.88	<5	10	<10	216	6468	5	321	<10	36	121
212356	1367310	0.007	<1	3.66	<2	96	2	14	5.56	8	52	80	149	11.06	0.18	49	2.44	2393	<1	95	803	14	1.41	7	<5	<10	213	5961	<2	294	10	34	168
212357	1367311	<0.005	2	4.96	9	41	2	24	6.17	8	54	84	97	10.61	0.26	46	2.61	2509	<1	89	930	9	0.82	<5	<5	<10	229	6834	<2	333	<10	39	122
212358	1367312	0.005	2	4.72	5	54	2	22	5.98	7	56	87	113	10.64	0.19	44	2.50	2432	<1	98	881	15	1.07	<5	<5	<10	256	7245	4	329	<10	37	137
212359	1367313	0.006	<1	5.10	<2	150	2	25	5.98	7	54	83	125	10.29	0.31	43	2.53	2530	<1	100	877	11	1.40	<5	7	<10	255	7781	<2	331	<10	37	149
212360	1367314	0.006	2	4.22	3	201	2	11	7.13	7	54	79	135	9.64	0.17	48	2.94	2445	<1	95	774	17	1.55	<5	5	<10	273	8131	4	314	<10	35	141
212361	1367315	0.024	<1	5.03	2	164	2	15	6.30	7	57	86	126	10.81	0.30	53	2.79	2377	<1	95	877	9	1.23	<5	6	<10	236	8152	<2	335	11	37	141
212362	1367316	0.006	<1	5.09	<2	66	2	11	6.05	8	73	73	247	12.29	0.23	52	2.87	2870	<1	85	918	11	1.96	<5	<5	<10	214	6461	16	333	10	40	151
212363	1367317	0.008	<1	5.33	<2	7	2	13	6.35	8	54	72	108	10.99	0.11	41	2.79	2397	<1	82	934	7	0.88	5	<5	<10	265	6540	2	348	<10	41	127
212364	1367318	0.009	<1	4.89	6	85	2	10	5.70	7	60	69	98	10.84	0.12	63	2.79	2348	<1	89	969	10	1.01	<5	<5	<10	264	5711	6	330	<10	40	138
212365R	1367318	0.008	<1	5.43	<2	68	2	15	5.74	7	58	79	95	10.65	0.18	61	2.72	2348	<1	100	964	15	0.94	<5	<5	<10	281	6121	2	338	<10	41	138
212366	1367319	<0.005	<1	5.37	3	218	6	7	2.67	<4	14	37	26	3.49	0.18	88	0.94	690	<1	61	530	5	0.69	<5	5	<10	273	2738	<2	89	<10	14	58
212367	1367320	<0.005	<1	4.39	7	411	<2	6	2.34	<4	17	62	27	3.52	0.15	14	1.47	709	<1	51	686	6	0.59	<5	<5	<10	296	2888	<2	118	23	17	52

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/24/2012
 Date Completed: 08/10/2012
 Job #: 201242807
 Reference: TL12254
 Sample #: 255

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
212368	1367321	0.011	<1	3.64	5	280	3	11	1.24	<4	6	27	24	1.38	0.17	51	0.47	271	<1	59	402	10	0.56	<5	<5	<10	227	1591	<2	23	<10	5	41
212369	1367322	0.009	<1	4.67	5	331	3	8	1.45	<4	6	34	18	1.46	0.12	57	0.50	291	<1	69	453	7	0.71	<5	<5	<10	256	1646	<2	23	<10	6	57
212370	1367323	<0.005	<1	3.41	<2	333	4	16	1.41	<4	7	29	12	1.50	0.09	61	0.77	410	<1	62	392	25	0.59	<5	<5	<10	220	1475	<2	23	<10	5	54
212371	1367324	0.009	<1	4.91	5	384	<2	15	1.70	<4	5	31	15	1.60	0.24	53	0.80	356	<1	61	384	32	0.82	5	<5	<10	257	1530	<2	25	<10	6	144
212372	1367325	<0.005	<1	2.61	3	342	<2	5	1.05	<4	6	34	7	1.51	0.18	47	0.54	327	<1	68	381	2	0.48	<5	<5	<10	154	1598	<2	25	<10	4	45
212373	1367326	0.007	<1	5.17	4	326	<2	11	1.43	<4	6	30	7	1.44	0.17	51	0.59	321	<1	58	410	7	0.70	<5	<5	<10	209	1587	<2	24	<10	6	42
212374	1367327	0.061	<1	2.47	2	127	2	21	8.96	8	26	46	114	11.25	0.27	20	3.68	2743	<1	78	451	15	3.66	<5	<5	<10	263	4243	<2	137	11	21	291
212375	1367328	0.020	<1	4.58	<2	552	2	6	1.32	<4	10	82	55	2.53	0.10	56	1.00	508	<1	153	339	11	1.09	<5	<5	<10	209	1316	<2	30	<10	6	75
212376D	1367328	0.021	<1	5.49	4	565	<2	8	1.48	<4	9	86	55	2.54	0.12	58	1.02	508	<1	166	339	8	1.19	<5	<5	<10	229	1350	<2	31	<10	6	77
212377	1367329	0.080	<1	5.40	<2	188	2	19	6.02	10	58	106	242	11.57	0.21	66	2.81	2416	5	141	904	14	2.49	<5	<5	<10	258	7074	<2	325	10	39	547
212378	1367330	0.012	<1	5.38	2	59	2	12	5.74	7	55	89	127	9.86	0.16	45	2.36	2187	<1	118	917	11	0.87	<5	<5	<10	287	6917	<2	321	<10	39	128
212379	1367331	0.044	<1	4.84	4	108	3	17	5.77	8	54	93	104	11.28	0.16	50	2.55	2584	<1	127	811	21	1.19	<5	<5	<10	229	6717	<2	303	<10	36	153
212380	1367332	0.016	1	4.29	<2	71	2	15	5.31	7	50	94	84	10.49	0.15	41	2.51	2756	<1	113	839	15	1.09	<5	<5	<10	263	6023	<2	294	<10	34	131
212381	1367333	1.733	2	4.22	<2	60	2	14	6.31	10	58	73	169	14.05	0.13	39	2.67	3489	5	104	742	19	2.19	<5	<5	<10	200	6369	4	273	<10	33	152
212382	1367334	0.036	1	5.66	5	69	2	17	5.86	8	56	88	117	11.22	0.23	36	2.39	2881	<1	110	931	12	1.09	<5	10	<10	268	7190	<2	331	<10	38	122
212383	1367335	0.042	<1	5.13	3	76	2	13	5.90	8	57	79	159	11.54	0.28	32	2.30	2955	<1	96	913	13	1.29	<5	<5	<10	295	7391	<2	332	<10	37	156
212384	1367336	0.009	<1	5.31	<2	222	<2	18	4.18	5	35	61	91	6.91	0.22	35	1.64	1468	<1	93	726	15	1.09	<5	7	<10	285	5144	<2	185	<10	22	108
212385	1367337	<0.005	<1	5.43	<2	22	2	26	6.32	8	55	80	123	11.56	0.32	36	2.87	2724	<1	96	917	14	0.86	<5	<5	<10	336	7098	6	337	10	38	126
212386	1367338	0.009	<1	5.29	2	109	2	20	6.04	8	57	85	110	10.67	0.14	38	2.64	2434	<1	100	928	7	0.84	<5	5	<10	297	7240	<2	341	<10	37	127
212387D	1367338	0.030	<1	4.59	<2	106	2	15	5.70	7	54	83	111	10.21	0.32	36	2.53	2313	<1	98	923	13	0.79	<5	8	<10	265	6575	<2	320	<10	36	141

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/24/2012
 Date Completed: 08/10/2012
 Job #: 201242807
 Reference: TL12254
 Sample #: 255

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
212388	1367339	0.007	<1	4.03	3	201	2	15	3.95	4	32	49	75	6.01	0.40	41	1.95	1348	<1	64	653	10	0.76	<5	<5	<10	217	4503	<2	179	<10	22	117
212389	1367340	4.665	60	2.63	30	444	<2	8	1.19	21	16	40	60	3.22	0.34	10	0.90	518	<1	43	614	664	0.84	49	<5	254	228	1844	<2	90	58	13	1901
212390	1367341	0.068	<1	5.09	<2	121	2	21	6.49	8	56	87	119	10.94	0.38	45	2.56	2734	<1	103	958	11	1.09	<5	<5	<10	277	7203	6	331	<10	38	169
212391	1367342	0.031	<1	4.53	3	120	2	17	6.14	8	58	94	129	11.16	0.27	39	2.27	2311	<1	112	902	14	1.11	<5	<5	<10	277	6199	<2	345	<10	40	159
212392	1367343	0.032	<1	4.30	<2	104	2	17	5.98	8	57	91	144	10.79	0.29	39	2.40	2273	<1	110	873	9	1.04	<5	<5	<10	255	6149	<2	329	<10	38	161
212393	1367344	0.033	<1	4.63	<2	69	2	17	6.00	7	58	80	110	10.43	0.24	34	2.24	2193	<1	87	855	13	1.00	<5	<5	<10	310	6546	<2	335	<10	38	132
212394	1367345	0.310	1	3.96	<2	77	2	21	6.19	8	60	83	178	11.71	0.19	31	2.23	2359	<1	103	790	13	1.83	<5	<5	<10	311	6542	<2	310	<10	36	138
212395	1367346	0.086	1	4.65	6	36	2	14	7.32	8	56	78	149	11.10	0.23	35	2.41	2573	<1	84	857	3	0.93	<5	<5	<10	326	7137	<2	330	<10	39	131
212396	1367347	0.171	<1	4.20	2	51	2	13	6.34	7	55	90	108	10.67	0.12	33	2.49	2343	<1	103	900	15	0.77	<5	<5	<10	277	6666	2	332	10	38	132
212397	1367348	0.139	<1	3.99	<2	83	2	15	6.32	8	53	81	151	11.35	0.15	45	2.76	2387	<1	92	828	14	1.40	<5	<5	<10	250	6357	<2	315	<10	37	145
212398D	1367348	0.069	<1	4.19	<2	86	2	16	6.54	8	54	84	154	11.71	0.17	46	2.84	2469	<1	101	859	10	1.44	<5	<5	<10	261	6746	<2	325	<10	38	150
212399	1367349	0.079	<1	3.75	<2	51	2	18	6.47	8	59	90	152	12.07	0.37	32	2.11	2504	<1	124	863	18	2.16	<5	<5	<10	304	6495	<2	303	<10	38	149
212400	1367350	0.917	2	5.69	<2	83	2	17	6.45	8	55	97	109	11.61	0.45	45	2.38	2435	2	121	908	14	1.41	<5	<5	<10	312	6827	<2	325	<10	41	158
212401	1367351	0.054	<1	4.31	<2	54	2	12	6.68	8	61	83	138	11.03	0.34	27	2.20	2366	<1	112	877	13	1.53	<5	<5	<10	284	6441	<2	307	<10	38	136
212402	1367352	0.012	5	4.42	2	76	2	16	6.71	6	55	81	81	9.44	0.28	29	2.23	2293	<1	108	872	9	0.99	<5	<5	<10	322	6129	<2	301	<10	38	141
212403	1367353	0.031	<1	5.31	<2	75	<2	11	7.11	7	57	83	79	10.37	0.18	30	2.23	2391	<1	114	901	8	0.91	<5	<5	<10	315	7175	<2	315	<10	39	143
212404	1367354	0.043	2	5.50	<2	78	3	15	6.67	7	60	75	107	10.28	0.28	34	2.27	2298	<1	102	886	14	1.03	<5	<5	<10	320	6935	<2	318	<10	39	157
212405	1367355	0.020	4	5.29	<2	90	2	14	6.39	7	56	77	92	10.14	0.24	35	2.42	2013	<1	103	923	15	0.95	<5	<5	<10	297	5980	<2	317	<10	39	143
212406	1367356	0.028	<1	5.13	<2	144	2	11	5.80	6	56	78	122	9.73	0.25	45	2.32	1844	<1	93	876	12	1.21	<5	<5	<10	241	6744	<2	309	<10	37	125
212407	1367357	0.011	<1	4.43	3	37	2	19	6.71	7	60	71	100	10.73	0.18	27	2.14	2125	<1	85	880	8	0.81	<5	8	<10	253	7878	<2	322	<10	37	138

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/24/2012
 Date Completed: 08/10/2012
 Job #: 201242807
 Reference: TL12254
 Sample #: 255

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
212408	1367358	0.009	<1	3.90	<2	49	2	17	6.44	7	57	75	92	10.45	0.14	26	2.12	2053	<1	99	862	9	0.89	<5	6	<10	233	7747	<2	307	<10	37	125
212409D	1367358	0.014	5	4.75	<2	54	2	12	6.55	7	59	71	93	10.51	0.22	29	2.16	2078	<1	79	885	16	1.03	<5	<5	<10	243	8169	<2	315	<10	38	126
212410	1367359	0.011	<1	5.30	<2	48	2	18	6.52	7	59	78	64	10.68	0.21	27	2.13	2066	<1	93	858	8	0.85	<5	8	<10	244	8131	<2	327	16	39	124
212411	1367360	<0.005	<1	3.77	<2	383	<2	10	2.31	<4	18	63	27	3.56	0.38	13	1.47	708	<1	51	697	7	0.50	<5	<5	<10	272	2741	<2	118	20	16	55
212412	1367361	0.023	<1	5.70	5	152	3	20	6.75	8	62	75	128	11.04	0.52	66	2.76	2396	<1	98	842	14	1.73	<5	<5	<10	283	7578	2	332	<10	38	123
212413	1367362	0.028	2	4.45	7	59	2	16	5.93	7	55	72	87	10.05	0.32	35	2.33	2188	<1	88	861	9	1.06	5	<5	<10	218	6225	<2	310	<10	36	126
212414	1367363	0.047	<1	5.15	5	88	2	14	5.54	8	54	73	104	11.32	0.30	55	2.29	2293	<1	90	872	18	1.26	5	<5	<10	252	5333	<2	311	<10	37	136
212415	1367364	0.075	2	4.01	<2	79	2	12	5.79	8	58	71	138	10.75	0.24	46	2.23	1968	<1	94	835	10	1.54	<5	<5	<10	259	4966	<2	295	<10	36	122
212416	1367365	0.014	<1	5.29	4	161	2	16	6.18	8	56	75	129	11.05	0.25	41	2.10	2108	<1	88	858	4	1.12	<5	7	<10	258	6065	<2	315	<10	38	134
212417	1367366	0.018	<1	4.72	<2	172	2	20	6.17	7	56	74	90	10.77	0.20	38	2.01	2075	<1	91	877	8	0.96	<5	<5	<10	243	5934	<2	304	<10	37	132
212418	1367367	<0.005	<1	4.13	2	378	<2	9	1.64	<4	7	15	12	1.69	0.26	42	0.64	362	<1	37	390	7	0.66	<5	<5	<10	162	1648	<2	33	<10	6	32
212419	1367368	0.012	<1	3.36	7	325	<2	11	1.06	<4	6	23	5	1.48	0.17	45	0.80	350	<1	58	402	4	0.71	<5	6	<10	128	1416	<2	25	<10	5	34
212420D	1367368	0.010	<1	4.11	5	338	<2	8	1.16	<4	5	22	5	1.48	0.18	48	0.82	352	<1	56	409	5	0.76	<5	<5	<10	141	1417	<2	25	<10	5	35
212421	1367369	0.006	<1	1.81	<2	243	<2	5	0.79	<4	6	17	8	1.39	0.12	46	0.87	372	<1	42	390	5	0.51	<5	<5	<10	100	1340	<2	23	<10	4	34
212422	1367370	<0.005	<1	5.01	6	336	<2	10	1.89	<4	5	23	4	1.55	0.20	51	1.13	484	<1	47	421	5	0.57	<5	<5	<10	169	1512	<2	29	<10	6	43
212423	1367371	<0.005	<1	2.99	<2	355	<2	11	1.19	<4	7	18	12	1.55	0.28	37	0.76	331	<1	45	444	6	0.58	<5	<5	<10	135	1483	<2	28	<10	5	33
212424	1367372	0.008	<1	5.49	9	81	2	17	5.98	7	50	69	95	10.21	0.32	35	2.48	1481	<1	82	861	9	0.82	<5	5	<10	252	6010	<2	300	<10	38	117
212425	1367373	0.008	<1	4.63	<2	95	<2	20	6.26	7	50	65	106	10.38	0.40	35	2.59	1564	<1	77	901	11	0.81	<5	6	<10	267	5338	<2	303	<10	37	137
212426	1367374	0.006	2	4.88	5	53	2	19	6.62	7	50	70	110	10.53	0.27	29	2.48	1616	<1	91	940	16	0.77	<5	<5	<10	315	6106	<2	308	<10	39	116
212427	1367375	0.006	<1	5.72	5	75	2	10	6.16	8	54	67	139	10.74	0.31	38	2.59	1568	<1	79	872	11	0.99	<5	7	<10	268	6268	19	317	<10	39	119

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/24/2012
 Date Completed: 08/10/2012
 Job #: 201242807
 Reference: TL12254
 Sample #: 255

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
212428	1367376	0.005	<1	4.63	<2	108	2	21	5.78	7	49	70	162	10.39	0.29	40	2.40	1542	<1	84	820	15	0.97	<5	<5	<10	253	6014	<2	290	<10	36	123
212429	1367377	<0.005	<1	3.49	<2	87	2	18	5.45	7	50	72	119	9.99	0.25	27	2.23	1513	<1	95	872	9	0.65	<5	<5	<10	214	4913	<2	307	<10	37	120
212430	1367378	0.013	<1	4.98	<2	100	2	14	5.96	7	59	71	131	10.15	0.26	32	2.31	1737	<1	84	878	9	0.93	<5	<5	<10	273	5938	<2	322	<10	38	127
212431R	1367378	0.022	<1	4.68	<2	109	2	9	5.91	7	55	76	132	10.18	0.27	32	2.31	1750	<1	97	887	10	0.85	5	<5	<10	271	6004	<2	326	<10	38	129
212432	1367379	0.047	<1	4.64	4	122	2	26	5.43	8	52	66	158	12.33	0.27	60	3.01	2693	<1	82	877	17	1.58	<5	<5	<10	204	6093	<2	295	<10	37	173
212433	1367380	2.043	<1	3.44	6	416	<2	16	2.16	<4	18	62	37	3.90	0.19	12	1.48	747	<1	55	702	10	0.44	<5	<5	<10	264	2833	<2	122	25	16	62
212434	1367381	0.020	<1	4.75	<2	122	2	22	6.26	7	58	67	140	10.40	0.28	38	2.33	1936	<1	89	842	17	1.19	<5	<5	<10	277	7359	<2	308	<10	37	139
212435	1367382	0.021	<1	5.44	<2	54	2	18	6.19	8	57	75	95	10.89	0.35	38	2.14	2127	<1	90	892	12	0.89	<5	<5	<10	268	6259	<2	326	<10	38	140
212436	1367383	0.014	<1	5.03	7	199	2	6	3.77	<4	24	40	41	4.23	0.27	52	1.77	1289	<1	64	577	11	0.75	<5	<5	<10	199	3318	<2	110	<10	14	55
212437	1367384	0.086	<1	4.32	3	121	2	15	5.88	7	53	71	136	10.50	0.29	61	3.37	2011	<1	77	864	10	1.52	<5	<5	<10	191	5570	8	299	<10	36	132
212438	1367385	0.210	<1	4.82	<2	122	2	19	5.62	7	46	66	84	10.23	0.26	55	2.53	2297	<1	88	845	10	1.06	<5	5	<10	190	5042	5	290	111	35	132
212439	1367386	0.242	<1	5.13	<2	173	2	15	5.57	9	55	66	138	12.31	0.30	54	2.37	2329	<1	85	864	13	1.22	<5	<5	<10	164	5261	<2	314	67	42	159
212440	1367387	0.024	<1	5.21	<2	151	2	19	6.15	8	54	75	82	11.08	0.26	44	2.11	2082	<1	85	974	10	0.72	<5	<5	<10	250	5158	<2	331	<10	39	133
212441	1367388	0.030	<1	5.25	<2	350	2	14	5.27	8	58	84	137	11.15	0.25	57	2.11	1990	<1	98	1218	14	1.11	<5	<5	<10	234	4841	<2	319	<10	39	131
212442D	1367388	0.042	<1	5.30	<2	362	2	20	5.30	8	59	84	137	11.22	0.23	58	2.14	1989	<1	103	1236	10	1.11	<5	<5	<10	235	4933	<2	323	<10	39	136
212443	1367389	0.013	<1	4.28	4	168	<2	22	5.78	7	53	81	107	10.42	0.23	37	1.99	1776	<1	95	898	12	0.72	<5	<5	<10	253	5215	<2	309	<10	37	128
212444	1367390	0.017	<1	4.32	<2	<1	2	16	5.22	5	44	344	68	7.82	0.22	47	3.65	1366	<1	182	1134	11	0.64	<5	<5	<10	314	4296	<2	232	<10	28	97
212445	1367391	0.511	<1	2.44	6	<1	2	8	5.12	4	47	610	17	6.25	0.10	58	6.03	1224	<1	457	1070	13	0.42	<5	<5	<10	224	2690	<2	135	<10	18	75
212446	1367392	0.069	<1	2.81	4	20	<2	29	5.03	4	47	543	11	6.28	0.21	65	5.75	1181	<1	417	1114	12	0.46	<5	<5	<10	242	3891	<2	141	<10	19	81
212447	1367393	0.040	<1	5.34	<2	35	<2	12	6.07	6	52	188	94	9.58	0.25	58	3.28	2261	<1	153	996	12	1.09	<5	<5	<10	327	5835	<2	277	<10	34	132

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Friday, June 15, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/01/2012
 Date Completed: 06/15/2012
 Job #: 201241886
 Reference: TL12 255
 Sample #: 301

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
156386	1360001	65	0.002	0.065
156387	1360002	86	0.003	0.086
156388	1360003	136	0.004	0.136
156389	1360004	37	0.001	0.037
156390	1360005	24	<0.001	0.024
156391	1360006	7	<0.001	0.007
156392	1360007	129	0.004	0.129
156393	1360008	<5	<0.001	<0.005
156394	1360009	<5	<0.001	<0.005
156395	1360010	6	<0.001	0.006
156396 Dup	1360010	Insufficient Sample		
156397	1360011	18	<0.001	0.018
156398	1360012	121	0.004	0.121
156399	1360013	179	0.005	0.179
156400	1360014	101	0.003	0.101
156401	1360015	70	0.002	0.070
156402	1360016	25	<0.001	0.025
156403	1360017	1280	0.037	1.280
156404	1360018	57	0.002	0.057
156405	1360019	123	0.004	0.123
156406	1360020	214	0.006	0.214
156407 Dup	1360020	Insufficient Sample		
156408	1360021	222	0.006	0.222
156409	1360022	444	0.013	0.444
156410	1360023	40	0.001	0.040
156411	1360024	48	0.001	0.048
156412	1360025	34	<0.001	0.034
156413	1360026	871	0.025	0.871
156414	1360027	107	0.003	0.107
156415	1360028	9	<0.001	0.009

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

The results included on this report relate only to the items tested.

The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 15, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/01/2012
 Date Completed: 06/15/2012
 Job #: 201241886
 Reference: TL12 255
 Sample #: 301

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
156416	1360029	40	0.001	0.040
156417	1360030	6	<0.001	0.006
156418 Dup	1360030	Insufficient Sample		
156419	1360031	88	0.003	0.088
156420	1360032	119	0.003	0.119
156421	1360033	86	0.003	0.086
156422	1360034	1512	0.044	1.512
156423	1360035	33	<0.001	0.033
156424	1360036	18	<0.001	0.018
156425	1360037	9	<0.001	0.009
156426	1360038	31	<0.001	0.031
156427	1360039	114	0.003	0.114
156428	1360040	1924	0.056	1.924
156429 Dup	1360040	Insufficient Sample		
156430	1360041	19	<0.001	0.019
156431	1360042	12	<0.001	0.012
156432	1360043	12	<0.001	0.012
156433	1360044	7	<0.001	0.007
156434	1360045	24	<0.001	0.024
156435	1360046	333	0.010	0.333
156436	1360047	22	<0.001	0.022
156437	1360048	694	0.020	0.694
156438	1360049	20	<0.001	0.020
156439	1360050	<5	<0.001	<0.005
156440 Dup	1360050	Insufficient Sample		
156441	1360051	9	<0.001	0.009
156442	1360052	11	<0.001	0.011
156443	1360053	154	0.004	0.154
156444	1360054	17	<0.001	0.017
156445	1360055	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 15, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/01/2012
 Date Completed: 06/15/2012
 Job #: 201241886
 Reference: TL12 255
 Sample #: 301

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
156446	1360056	6	<0.001	0.006
156447	1360057	58	0.002	0.058
156448	1360058	38	0.001	0.038
156449	1360059	43	0.001	0.043
156450	1360060	4912	0.143	4.912
156451 Rep	1360060	Insufficient Sample		
156452	1360061	54	0.002	0.054
156453	1360062	34	<0.001	0.034
156454	1360063	8	<0.001	0.008
156455	1360064	23	<0.001	0.023
156456	1360065	42	0.001	0.042
156457	1360066	535	0.016	0.535
156458	1360067	86	0.003	0.086
156459	1360068	76	0.002	0.076
156460	1360069	18	<0.001	0.018
156461	1360070	12	<0.001	0.012
156462 Dup	1360070	Insufficient Sample		
156463	1360071	15	<0.001	0.015
156464	1360072	9	<0.001	0.009
156465	1360073	19	<0.001	0.019
156466	1360074	17	<0.001	0.017
156467	1360075	14	<0.001	0.014
156468	1360076	13	<0.001	0.013
156469	1360077	14	<0.001	0.014
156470	1360078	19	<0.001	0.019
156471	1360079	10	<0.001	0.010
156472	1360080	250	0.007	0.250
156473 Dup	1360080	Insufficient Sample		
156474	1360081	40	0.001	0.040
156475	1360082	9	<0.001	0.009

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 15, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/01/2012
 Date Completed: 06/15/2012
 Job #: 201241886
 Reference: TL12 255
 Sample #: 301

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
156476	1360083	19	<0.001	0.019
156477	1360084	14	<0.001	0.014
156478	1360085	17	<0.001	0.017
156479	1360086	28	<0.001	0.028
156480	1360087	15	<0.001	0.015
156481	1360088	17	<0.001	0.017
156482	1360089	39	0.001	0.039
156483	1360090	<5	<0.001	<0.005
156484 Dup	1360090	Insufficient Sample		
156485	1360091	29	<0.001	0.029
156486	1360092	20	<0.001	0.020
156487	1360093	17	<0.001	0.017
156488	1360094	24	<0.001	0.024
156489	1360095	8	<0.001	0.008
156490	1360096	8	<0.001	0.008
156491	1360097	18	<0.001	0.018
156492	1360098	43	0.001	0.043
156493	1360099	18	<0.001	0.018
156494	1360100	2002	0.058	2.002
156495 Dup	1360100	Insufficient Sample		
156496	1360101	23	<0.001	0.023
156497	1360102	27	<0.001	0.027
156498	1360103	29	<0.001	0.029
156499	1360104	14	<0.001	0.014
156500	1360105	9	<0.001	0.009
156501	1360106	15	<0.001	0.015
156502	1360107	54	0.002	0.054
156503	1360108	14	<0.001	0.014
156504	1360109	18	<0.001	0.018
156505	1360110	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 15, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/01/2012
 Date Completed: 06/15/2012
 Job #: 201241886
 Reference: TL12 255
 Sample #: 301

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
156506 Dup	1360110	Insufficient Sample		
156507	1360111	20	<0.001	0.020
156508	1360112	15	<0.001	0.015
156509	1360113	14	<0.001	0.014
156510	1360114	18	<0.001	0.018
156511	1360115	15	<0.001	0.015
156512	1360116	16	<0.001	0.016
156513	1360117	13	<0.001	0.013
156514	1360118	14	<0.001	0.014
156515	1360119	9	<0.001	0.009
156516	1360120	5046	0.147	5.046
156517 Rep	1360120	Insufficient Sample		
156518	1360121	5	<0.001	0.005
156519	1360122	7	<0.001	0.007
156520	1360123	10	<0.001	0.010
156521	1360124	8	<0.001	0.008
156522	1360125	8	<0.001	0.008
156523	1360126	8	<0.001	0.008
156524	1360127	9	<0.001	0.009
156525	1360128	12	<0.001	0.012
156526	1360129	12	<0.001	0.012
156527	1360130	7	<0.001	0.007
156528 Dup	1360130	Insufficient Sample		
156529	1360131	14	<0.001	0.014
156530	1360132	12	<0.001	0.012
156531	1360133	17	<0.001	0.017
156532	1360134	12	<0.001	0.012
156533	1360135	9	<0.001	0.009
156534	1360136	14	<0.001	0.014
156535	1360137	21	<0.001	0.021

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.

The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 15, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/01/2012
 Date Completed: 06/15/2012
 Job #: 201241886
 Reference: TL12 255
 Sample #: 301

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
156536	1360138	28	<0.001	0.028
156537	1360139	24	<0.001	0.024
156538	1360140	243	0.007	0.243
156539 Dup	1360140	Insufficient Sample		
156540	1360141	21	<0.001	0.021
156541	1360142	76	0.002	0.076
156542	1360143	26	<0.001	0.026
156543	1360144	16	<0.001	0.016
156544	1360145	38	0.001	0.038
156545	1360146	20	<0.001	0.020
156546	1360147	34	<0.001	0.034
156547	1360148	44	0.001	0.044
156548	1360149	22	<0.001	0.022
156549	1360150	<5	<0.001	<0.005
156550 Dup	1360150	Insufficient Sample		
156551	1360151	7	<0.001	0.007
156552	1360152	13	<0.001	0.013
156553	1360153	16	<0.001	0.016
156554	1360154	9	<0.001	0.009
156555	1360155	25	<0.001	0.025
156556	1360156	13	<0.001	0.013
156557	1360157	9	<0.001	0.009
156558	1360158	7	<0.001	0.007
156559	1360159	13	<0.001	0.013
156560	1360160	2038	0.059	2.038
156561 Dup	1360160	Insufficient Sample		
156562	1360161	<5	<0.001	<0.005
156563	1360162	<5	<0.001	<0.005
156564	1360163	7	<0.001	0.007
156565	1360164	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 15, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/01/2012
 Date Completed: 06/15/2012
 Job #: 201241886
 Reference: TL12 255
 Sample #: 301

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
156566	1360165	6	<0.001	0.006
156567	1360166	17	<0.001	0.017
156568	1360167	12	<0.001	0.012
156569	1360168	18	<0.001	0.018
156570	1360169	<5	<0.001	<0.005
156571	1360170	5	<0.001	0.005
156572 Dup	1360170	Insufficient Sample		
156573	1360171	<5	<0.001	<0.005
156574	1360172	7	<0.001	0.007
156575	1360173	17	<0.001	0.017
156576	1360174	57	0.002	0.057
156577	1360175	142	0.004	0.142
156578	1360176	127	0.004	0.127
156579	1360177	185	0.005	0.185
156580	1360178	41	0.001	0.041
156581	1360179	8	<0.001	0.008
156582	1360180	5357	0.156	5.357
156583 Rep	1360180	Insufficient Sample		
156584	1360181	11	<0.001	0.011
156585	1360182	157	0.005	0.157
156586	1360183	123	0.004	0.123
156587	1360184	20	<0.001	0.020
156588	1360185	8	<0.001	0.008
156589	1360186	16	<0.001	0.016
156590	1360187	21	<0.001	0.021
156591	1360188	22	<0.001	0.022
156592	1360189	16	<0.001	0.016
156593	1360190	<5	<0.001	<0.005
156594 Dup	1360190	Insufficient Sample		
156595	1360191	20	<0.001	0.020

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 15, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/01/2012
 Date Completed: 06/15/2012
 Job #: 201241886
 Reference: TL12 255
 Sample #: 301

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
156596	1360192	43	0.001	0.043
156597	1360193	16	<0.001	0.016
156598	1360194	46	0.001	0.046
156599	1360195	25	<0.001	0.025
156600	1360196	25	<0.001	0.025
156601	1360197	19	<0.001	0.019
156602	1360198	18	<0.001	0.018
156603	1360199	22	<0.001	0.022
156604	1360200	260	0.008	0.260
156605 Dup	1360200	Insufficient Sample		
156606	1360201	16	<0.001	0.016
156607	1360202	24	<0.001	0.024
156608	1360203	42	0.001	0.042
156609	1360204	45	0.001	0.045
156610	1360205	19	<0.001	0.019
156611	1360206	272	0.008	0.272
156612	1360207	595	0.017	0.595
156613	1360208	42	0.001	0.042
156614	1360209	10	<0.001	0.010
156615	1360210	7	<0.001	0.007
156616 Dup	1360210	Insufficient Sample		
156617	1360211	153	0.004	0.153
156618	1360212	1199	0.035	1.199
156619	1360213	215	0.006	0.215
156620	1360214	22	<0.001	0.022
156621	1360215	40	0.001	0.040
156622	1360216	23	<0.001	0.023
156623	1360217	36	0.001	0.036
156624	1360218	46	0.001	0.046
156625	1360219	103	0.003	0.103

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 15, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/01/2012
 Date Completed: 06/15/2012
 Job #: 201241886
 Reference: TL12 255
 Sample #: 301

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
156626	1360220	1916	0.056	1.916
156627 Dup	1360220	Insufficient Sample		
156628	1360221	535	0.016	0.535
156629	1360222	18	<0.001	0.018
156630	1360223	16	<0.001	0.016
156631	1360224	29	<0.001	0.029
156632	1360225	24	<0.001	0.024
156633	1360226	24	<0.001	0.024
156634	1360227	43	0.001	0.043
156635	1360228	53	0.002	0.053
156636	1360229	81	0.002	0.081
156637	1360230	8	<0.001	0.008
156638 Dup	1360230	Insufficient Sample		
156639	1360231	48	0.001	0.048
156640	1360232	332	0.010	0.332
156641	1360233	41	0.001	0.041
156642	1360234	21	<0.001	0.021
156643	1360235	39	0.001	0.039
156644	1360236	30	<0.001	0.030
156645	1360237	17	<0.001	0.017
156646	1360238	30	<0.001	0.030
156647	1360239	59	0.002	0.059
156648	1360240	5600	0.163	5.600
156649 Rep	1360240	Insufficient Sample		
156650	1360241	56	0.002	0.056
156651	1360242	67	0.002	0.067
156652	1360243	100	0.003	0.100
156653	1360244	32	<0.001	0.032
156654	1360245	21	<0.001	0.021
156655	1360246	27	<0.001	0.027

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 15, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/01/2012
 Date Completed: 06/15/2012
 Job #: 201241886
 Reference: TL12 255
 Sample #: 301

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
156656	1360247	22	<0.001	0.022
156657	1360248	19	<0.001	0.019
156658	1360249	17	<0.001	0.017
156659	1360250	8	<0.001	0.008
156660 Dup	1360250	Insufficient Sample		
156661	1360251	25	<0.001	0.025
156662	1360252	22	<0.001	0.022
156663	1360253	12	<0.001	0.012
156664	1360254	159	0.005	0.159
156665	1360255	62	0.002	0.062
156666	1360256	18	<0.001	0.018
156667	1360257	12	<0.001	0.012
156668	1360258	112	0.003	0.112
156669	1360259	33	<0.001	0.033
156670	1360260	218	0.006	0.218
156671 Dup	1360260	Insufficient Sample		
156672	1360261	14	<0.001	0.014
156673	1360262	47	0.001	0.047
156674	1360263	25	<0.001	0.025
156675	1360264	24	<0.001	0.024
156676	1360265	16	<0.001	0.016
156677	1360266	11	<0.001	0.011
156678	1360267	10	<0.001	0.010
156679	1360268	14	<0.001	0.014
156680	1360269	8	<0.001	0.008
156681	1360270	<5	<0.001	<0.005
156682 Dup	1360270	Insufficient Sample		
156683	1360271	7	<0.001	0.007
156684	1360272	17	<0.001	0.017
156685	1360273	16	<0.001	0.016

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 15, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/01/2012
 Date Completed: 06/15/2012
 Job #: 201241886
 Reference: TL12 255
 Sample #: 301

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
156686	1360274	16	<0.001	0.016
156687	1360275	24	<0.001	0.024
156688	1360276	27	<0.001	0.027
156689	1360277	431	0.013	0.431
156690	1360278	28	<0.001	0.028
156691	1360279	37	0.001	0.037
156692	1360280	2083	0.061	2.083
156693 Dup	1360280	Insufficient Sample		
156694	1360281	33	<0.001	0.033
156695	1360282	78	0.002	0.078
156696	1360283	72	0.002	0.072
156697	1360284	209	0.006	0.209
156698	1360285	73	0.002	0.073
156699	1360286	123	0.004	0.123
156700	1360287	143	0.004	0.143
156701	1360288	25	<0.001	0.025
156702	1360289	81	0.002	0.081
156703	1360290	10	<0.001	0.010
156704 Dup	1360290	Insufficient Sample		
156705	1360291	33	<0.001	0.033
156706	1360292	16	<0.001	0.016
156707	1360293	7	<0.001	0.007
156708	1360294	31	<0.001	0.031
156709	1360295	37	0.001	0.037
156710	1360296	31	<0.001	0.031
156711	1360297	36	0.001	0.036
156712	1360298	112	0.003	0.112
156713	1360299	315	0.009	0.315
156714	1360300	4894	0.143	4.894
156715 Rep	1360300	Insufficient Sample		

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 15, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/01/2012
 Date Completed: 06/15/2012
 Job #: 201241886
 Reference: TL12 255
 Sample #: 301

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
156716	1360301	925	0.027	0.925

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.

The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 22, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/11/2012
 Date Completed: 06/22/2012
 Job #: 201242023
 Reference: TL 12256
 Sample #: 165

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
165079	1305072	18	<0.001	0.018
165080	1305073	29	<0.001	0.029
165081	1305074	12	<0.001	0.012
165082	1305075	8	<0.001	0.008
165083	1305076	12	<0.001	0.012
165084	1305077	98	0.003	0.098
165085	1305078	15	<0.001	0.015
165086	1305079	12	<0.001	0.012
165087	1305080	<5	<0.001	<0.005
165088	1305081	41	0.001	0.041
165089 Dup	1305081	34	0.001	0.034
165090	1305082	14	<0.001	0.014
165091	1305083	33	<0.001	0.033
165092	1305084	33	<0.001	0.033
165093	1305085	14	<0.001	0.014
165094	1305086	17	<0.001	0.017
165095	1305087	41	0.001	0.041
165096	1305088	93	0.003	0.093
165097	1305089	47	0.001	0.047
165098	1305090	5067	0.148	5.067
165099	1305091	645	0.019	0.645
165100 Dup	1305091	606	0.018	0.606
165101	1305092	172	0.005	0.172
165102	1305093	462	0.013	0.462
165103	1305094	51	0.001	0.051
165104	1305095	28	<0.001	0.028
165105	1305096	28	<0.001	0.028
165106	1305097	29	<0.001	0.029
165107	1305098	13	<0.001	0.013
165108	1305099	17	<0.001	0.017

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 22, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/11/2012
 Date Completed: 06/22/2012
 Job #: 201242023
 Reference: TL 12256
 Sample #: 165

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
165109	1305100	8	<0.001	0.008
165110	1305101	13	<0.001	0.013
165111 Dup	1305101	14	<0.001	0.014
165112	1305102	15	<0.001	0.015
165113	1305103	12	<0.001	0.012
165114	1305104	7	<0.001	0.007
165115	1305105	19	<0.001	0.019
165116	1305106	8	<0.001	0.008
165117	1305107	16	<0.001	0.016
165118	1305108	12	<0.001	0.012
165119	1305109	32	<0.001	0.032
165120	1305110	2372	0.069	2.372
165121	1305111	36	0.001	0.036
165122 Dup	1305111	32	<0.001	0.032
165123	1305112	52	0.002	0.052
165124	1305113	125	0.004	0.125
165125	1305114	31	<0.001	0.031
165126	1305115	33	<0.001	0.033
165127	1305116	33	<0.001	0.033
165128	1305117	49	0.001	0.049
165129	1305118	28	<0.001	0.028
165130	1305119	17	<0.001	0.017
165131	1305120	10	<0.001	0.010
165132	1305121	26	<0.001	0.026
165133 Dup	1305121	26	<0.001	0.026
165134	1305122	24	<0.001	0.024
165135	1305123	15	<0.001	0.015
165136	1305124	16	<0.001	0.016
165137	1305125	7	<0.001	0.007
165138	1305126	109	0.003	0.109

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 22, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/11/2012
 Date Completed: 06/22/2012
 Job #: 201242023
 Reference: TL 12256
 Sample #: 165

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
165139	1305127	246	0.007	0.246
165140	1305128	294	0.009	0.294
165141	1305129	1767	0.052	1.767
165142	1305130	231	0.007	0.231
165143	1305131	<5	<0.001	<0.005
165144 Rep	1305131	<5	<0.001	<0.005
165145	1305132	<5	<0.001	<0.005
165146	1305133	18	<0.001	0.018
165147	1305134	<5	<0.001	<0.005
165148	1305135	63	0.002	0.063
165149	1305136	143	0.004	0.143
165150	1305137	271	0.008	0.271
165151	1305138	175	0.005	0.175
165152	1305139	2204	0.064	2.204
165153	1305140	7	<0.001	0.007
165154	1305141	637	0.019	0.637
165155 Dup	1305141	635	0.019	0.635
165156	1305142	565	0.016	0.565
165157	1305143	784	0.023	0.784
165158	1305144	172	0.005	0.172
165159	1305145	495	0.014	0.495
165160	1305146	192	0.006	0.192
165161	1305147	261	0.008	0.261
165162	1305148	106	0.003	0.106
165163	1305149	130	0.004	0.130
165164	1305150	4940	0.144	4.940
165165	1305151	97	0.003	0.097
165166 Dup	1305151	102	0.003	0.102
165167	1305152	127	0.004	0.127
165168	1305153	51	0.001	0.051

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 22, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/11/2012
 Date Completed: 06/22/2012
 Job #: 201242023
 Reference: TL 12256
 Sample #: 165

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
165169	1305154	25	<0.001	0.025
165170	1305155	37	0.001	0.037
165171	1305156	70	0.002	0.070
165172	1305157	7	<0.001	0.007
165173	1305158	<5	<0.001	<0.005
165174	1305159	<5	<0.001	<0.005
165175	1305160	<5	<0.001	<0.005
165176	1305161	<5	<0.001	<0.005
165177 Dup	1305161	<5	<0.001	<0.005
165178	1305162	<5	<0.001	<0.005
165179	1305163	<5	<0.001	<0.005
165180	1305164	6	<0.001	0.006
165181	1305165	29	<0.001	0.029
165182	1305166	23	<0.001	0.023
165183	1305167	6	<0.001	0.006
165184	1305168	<5	<0.001	<0.005
165185	1305169	<5	<0.001	<0.005
165186	1305170	1904	0.056	1.904
165187	1305171	15	<0.001	0.015
165188 Dup	1305171	15	<0.001	0.015
165189	1305172	10	<0.001	0.010
165190	1305173	12	<0.001	0.012
165191	1305174	15	<0.001	0.015
165192	1305175	11	<0.001	0.011
165193	1305176	6	<0.001	0.006
165194	1305177	15	<0.001	0.015
165195	1305178	16	<0.001	0.016
165196	1305179	10	<0.001	0.010
165197	1305180	15	<0.001	0.015
165198	1305181	25	<0.001	0.025

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 22, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/11/2012
 Date Completed: 06/22/2012
 Job #: 201242023
 Reference: TL 12256
 Sample #: 165

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
165199 Dup	1305181	27	<0.001	0.027
165200	1305182	59	0.002	0.059
165201	1305183	33	<0.001	0.033
165202	1305184	28	<0.001	0.028
165203	1305185	75	0.002	0.075
165204	1305186	53	0.002	0.053
165205	1305187	32	<0.001	0.032
165206	1305188	20	<0.001	0.020
165207	1305189	20	<0.001	0.020
165208	1305190	237	0.007	0.237
165209	1305191	49	0.001	0.049
165210 Rep	1305191	55	0.002	0.055
165211	1305192	34	0.001	0.034
165212	1305193	44	0.001	0.044
165213	1305194	14	<0.001	0.014
165214	1305195	18	<0.001	0.018
165215	1305196	27	<0.001	0.027
165216	1305197	11	<0.001	0.011
165217	1305198	7	<0.001	0.007
165218	1305199	40	0.001	0.040
165219	1305200	<5	<0.001	<0.005
165220	1305201	18	<0.001	0.018
165221 Dup	1305201	15	<0.001	0.015
165222	1305202	28	<0.001	0.028
165223	1305203	228	0.007	0.228
165224	1305204	51	0.001	0.051
165225	1305205	75	0.002	0.075
165226	1305206	380	0.011	0.380
165227	1305207	809	0.024	0.809
165228	1305208	210	0.006	0.210

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.

The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 22, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/11/2012
 Date Completed: 06/22/2012
 Job #: 201242023
 Reference: TL 12256
 Sample #: 165

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
165229	1305209	1035	0.030	1.035
165230	1305210	4994	0.146	4.994
165231	1305211	88	0.003	0.088
165232 Dup	1305211	72	0.002	0.072
165233	1305212	622	0.018	0.622
165234	1305213	187	0.005	0.187
165235	1305214	137	0.004	0.137
165236	1305215	220	0.006	0.220
165237	1305216	151	0.004	0.151
165238	1305217	280	0.008	0.280
165239	1305218	505	0.015	0.505
165240	1305219	109	0.003	0.109
165241	1305220	<5	<0.001	<0.005
165242	1305221	70	0.002	0.070
165243 Dup	1305221	78	0.002	0.078
165244	1305222	20	<0.001	0.020
165245	1305223	22	<0.001	0.022
165246	1305224	283	0.008	0.283
165247	1305225	110	0.003	0.110
165248	1305226	71	0.002	0.071
165249	1305227	278	0.008	0.278
165250	1305228	55	0.002	0.055
165251	1305229	48	0.001	0.048
165252	1305230	2002	0.058	2.002
165253	1305231	14	<0.001	0.014
165254 Dup	1305231	13	<0.001	0.013
165255	1305232	201	0.006	0.201
165256	1305233	14	<0.001	0.014
165257	1305234	7	<0.001	0.007
165258	1305235	10	<0.001	0.010

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 22, 2012

Certificate of Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 06/11/2012
 Date Completed: 06/22/2012
 Job #: 201242023
 Reference: TL 12256
 Sample #: 165

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
165259	1305236	12	<0.001	0.012

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.

The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

The results generated by this procedure are not accredited at this time and therefore are informational only.

Monday, August 20, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/25/2012
 Date Completed: 08/20/2012
 Job #: 201242968
 Reference: TL12256
 Sample #: 19

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm		
224665	1305101	0.013	2	5.87	24	635	<2	3	1.09	<4	5	27	4	0.95	<0.01	9	0.50	238	6	28	207	21	0.72	<5	8	<10	175	1905	<2	34	<10	4	14		
224666	1305102	0.006	3	4.70	20	576	<2	3	0.92	<4	7	30	6	0.71	<0.01	8	0.48	234	6	31	249	31	0.43	<5	19	<10	200	1748	5	31	<10	3	37		
224667	1305103	0.005	2	4.56	19	468	<2	2	1.35	<4	7	24	9	0.51	<0.01	2	0.23	159	6	30	317	18	0.28	<5	10	<10	241	1491	3	29	<10	3	22		
224668	1305104	<0.005	2	7.10	20	518	<2	5	1.55	<4	9	31	12	0.69	<0.01	5	0.30	183	6	36	368	27	0.39	5	10	<10	284	1706	4	35	<10	5	70		
224669	1305105	0.018	2	7.05	22	670	<2	10	1.15	<4	9	38	18	1.02	<0.01	6	0.46	241	5	36	451	76	0.67	<5	9	<10	241	1897	<2	40	<10	6	128		
224670	1305106	<0.005	1	6.33	15	644	<2	10	1.06	<4	6	22	5	0.64	<0.01	4	0.39	152	4	32	419	20	0.15	<5	14	<10	264	1704	<2	33	<10	5	29		
224671	1305107	0.010	3	6.69	5	624	<2	1	2.29	<4	9	24	29	1.86	<0.01	5	0.58	430	5	25	491	21	0.43	<5	12	10	311	2108	12	41	<10	6	69		
224672	1305108	0.065	2	7.75	12	640	<2	5	2.00	<4	10	24	21	2.41	<0.01	5	0.85	712	3	33	604	29	0.71	<5	17	<10	263	2468	4	46	<10	8	98		
224673	1305109	0.026	2	6.86	12	673	<2	8	1.13	<4	10	43	16	2.01	<0.01	4	0.57	664	4	34	490	21	0.82	<5	8	<10	190	2301	4	43	<10	6	65		
224674	1305110	1.723	2	5.73	16	536	<2	10	2.48	<4	19	67	40	4.42	<0.01	4	1.36	806	6	38	674	15	0.08	<5	6	10	312	3620	<2	139	29	16	69		
224675D	1305110																																		
224676	1305111	0.036	2	4.79	20	599	<2	6	0.44	<4	10	23	17	1.50	<0.01	<1	0.35	373	5	28	419	32	0.82	<5	9	<10	136	2024	2	41	<10	5	46		
224677	1305112	0.063	3	5.65	27	600	<2	10	1.89	<4	9	25	28	2.17	<0.01	9	0.90	962	5	29	470	68	1.19	<5	6	<10	183	2181	8	45	<10	6	249		
224678	1305113	0.118	4	3.80	38	538	<2	<1	1.50	<4	7	29	69	2.05	<0.01	3	0.75	787	6	27	364	214	1.69	<5	<5	<10	132	2008	<2	39	13	4	717		
224679	1305114	0.023	2	4.28	33	503	<2	8	0.63	<4	7	20	10	1.88	<0.01	<1	0.47	425	3	25	396	35	1.64	<5	8	<10	112	2068	6	37	<10	5	62		
224680	1305115	0.029	2	4.77	26	601	<2	5	1.25	<4	10	23	19	1.96	<0.01	3	0.59	595	4	27	403	36	1.27	<5	11	<10	142	2294	6	42	<10	5	78		
224681	1305116	0.335	2	6.38	26	561	<2	8	1.14	<4	10	19	18	1.93	<0.01	<1	0.70	538	3	25	511	39	1.30	<5	7	<10	137	2145	<2	39	<10	7	69		
224682	1305117	0.042	3	8.03	31	605	<2	5	1.73	<4	9	24	33	2.07	<0.01	6	0.92	715	4	28	540	59	1.19	<5	15	<10	172	2321	<2	41	16	8	136		
224683	1305118	0.022	3	8.25	30	658	2	13	2.94	<4	16	44	38	1.86	<0.01	2	0.90	644	5	40	799	56	0.97	<5	6	<10	232	2115	7	46	<10	8	70		
224684	1305119	0.028	3	6.39	31	584	<2	7	1.46	<4	6	26	11	1.23	<0.01	12	0.77	499	7	27	596	118	0.52	<5	10	<10	144	2345	2	41	<10	5	97		

PROCEDURE CODES: ALM1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Sunday, July 15, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/11/2012
 Date Completed: 06/22/2012
 Job #: 201242024
 Reference: TL 12257
 Sample #: 95

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
165260	1305237	0.051	<1	2.10	28	405	<2	<1	0.82	<4	10	22	21	2.58	0.06	13	0.81	654	<1	41	649	543	1.61	<5	<5	<10	117	2098	<2	48	13	6	787
165261	1305238	0.403	2	7.57	39	1982	<2	<1	1.50	13	12	48	18	2.90	<0.01	25	0.86	553	27	71	577	1558	2.49	5	<5	<10	238	3748	4	66	38	9	3231
165262	1305239	0.065	<1	2.56	37	544	<2	<1	0.86	<4	9	45	7	2.34	0.12	10	0.81	630	2	77	581	77	1.14	<5	<5	<10	109	2086	<2	43	<10	5	373
165263	1305240	0.012	<1	1.90	3	215	<2	<1	1.90	<4	15	48	23	3.25	0.06	6	1.24	624	<1	33	566	7	0.16	<5	<5	<10	178	2312	4	107	19	15	56
165264	1305241	0.025	<1	2.52	12	418	<2	<1	0.28	<4	8	45	16	1.04	0.07	8	0.50	218	<1	71	216	27	0.52	<5	<5	<10	57	1496	<2	35	<10	4	45
165265	1305242	0.015	<1	1.44	6	308	<2	<1	0.10	<4	7	28	6	0.66	0.03	6	0.43	138	<1	52	194	11	0.44	<5	<5	<10	45	1327	3	25	<10	3	40
165266	1305243	0.009	<1	1.79	8	308	<2	<1	0.06	<4	6	32	4	0.73	<0.01	6	0.55	233	<1	59	190	10	0.51	<5	<5	<10	43	1271	5	22	<10	3	98
165267	1305244	0.014	<1	1.55	8	263	<2	<1	0.12	<4	5	31	5	0.74	0.05	7	0.54	239	<1	59	180	9	0.53	<5	<5	<10	47	1245	<2	21	<10	3	10
165268	1305245	0.014	<1	0.80	6	204	<2	6	0.19	<4	6	51	2	0.89	0.01	8	0.51	226	5	94	280	11	0.46	<5	<5	<10	48	1292	5	24	<10	3	14
165269	1305246	0.019	<1	1.36	8	273	<2	<1	0.15	<4	5	38	7	0.64	0.02	5	0.26	144	2	72	360	38	0.35	<5	<5	<10	51	1380	2	27	<10	3	46
165270D	1305246	0.055	<1	2.20	8	323	<2	<1	0.40	<4	6	29	7	0.59	<0.01	5	0.26	141	<1	57	358	43	0.34	<5	6	<10	103	1403	<2	28	<10	3	47
165271	1305247	0.012	<1	2.20	8	327	<2	<1	0.46	<4	7	42	28	0.60	<0.01	4	0.19	134	2	78	353	95	0.31	<5	<5	<10	115	1344	<2	25	<10	3	112
165272	1305248	0.016	<1	2.40	14	336	<2	<1	0.83	<4	6	30	16	0.66	0.06	4	0.28	210	<1	53	350	78	0.45	<5	<5	<10	137	1301	<2	26	<10	3	94
165273	1305249	0.013	<1	2.84	4	458	<2	<1	0.78	<4	6	53	6	0.80	0.09	8	0.37	187	4	94	352	20	0.25	<5	<5	<10	170	1423	2	28	<10	4	24
165274	1305250	0.223	<1	<0.01	396	>5000	<2	<1	0.57	<4	6	12	28	2.67	<0.01	<1	0.04	<100	5	16	<100	20	0.40	15	<5	<10	66	443	5	12	38	5	21
165275	1305251	0.082	<1	1.67	39	542	<2	<1	0.26	<4	4	23	14	1.30	0.03	1	0.41	268	<1	43	490	70	1.12	<5	<5	<10	70	1205	5	21	<10	4	88
165276	1305252	0.136	<1	3.17	29	442	<2	<1	0.23	<4	8	20	27	1.35	<0.01	5	0.39	232	<1	41	470	74	1.30	<5	<5	<10	70	1515	<2	26	<10	4	284
165277	1305253	0.039	<1	1.62	13	366	<2	6	0.22	<4	5	31	21	1.30	<0.01	10	0.63	539	<1	61	413	44	0.77	<5	<5	<10	46	1521	<2	27	<10	4	95
165278	1305254	0.036	<1	1.46	7	288	<2	5	0.78	<4	8	89	15	1.89	0.16	12	1.15	508	3	104	587	19	0.72	<5	<5	<10	56	1795	10	37	<10	6	60
165279	1305255	0.302	<1	2.15	17	451	<2	5	<0.01	<4	7	58	86	0.91	0.20	6	0.47	276	5	95	292	117	0.62	<5	5	<10	40	1143	<2	22	<10	3	350

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, July 15, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/11/2012
 Date Completed: 06/22/2012
 Job #: 201242024
 Reference: TL 12257
 Sample #: 95

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
165280	1305256	0.223	<1	1.85	18	465	<2	1	<0.01	<4	8	45	67	0.83	0.20	5	0.43	241	2	78	294	207	0.63	<5	<5	<10	36	1118	<2	21	<10	3	364
165281D	1305256	0.270	1	2.26	16	477	<2	<1	<0.01	<4	7	60	66	0.91	0.13	5	0.43	244	6	103	283	195	0.62	<5	<5	<10	39	1140	<2	22	<10	3	353
165282	1305257	0.266	7	2.17	28	453	<2	19	<0.01	4	14	50	44	0.99	0.22	5	0.49	260	3	92	353	296	0.82	<5	6	<10	28	1281	5	30	11	3	799
165283	1305258	0.066	<1	2.87	26	499	<2	<1	0.28	<4	17	47	19	1.35	0.23	11	0.96	524	1	84	480	56	1.18	<5	6	<10	48	1544	<2	41	<10	5	117
165284	1305259	0.040	<1	4.20	40	572	<2	<1	0.52	<4	8	32	18	1.55	0.14	11	0.77	415	<1	60	471	43	1.47	<5	<5	<10	71	1715	4	34	<10	5	83
165285	1305260	0.008	<1	0.53	2	161	<2	<1	1.68	<4	14	46	21	3.15	<0.01	4	1.18	602	<1	32	542	8	0.12	<5	<5	<10	141	2183	3	102	16	13	52
165286	1305261	0.480	11	1.84	18	422	<2	<1	<0.01	7	6	35	283	1.19	0.05	<1	0.22	<100	<1	57	318	1017	1.31	7	<5	<10	30	1055	<2	24	31	3	2543
165287	1305262	0.078	<1	2.46	16	415	<2	<1	0.42	<4	5	29	13	1.16	<0.01	5	0.62	353	<1	51	472	68	1.02	<5	<5	<10	51	1265	<2	27	<10	4	160
165288	1305263	0.039	<1	3.80	18	461	<2	2	0.79	<4	5	34	6	1.62	0.61	10	0.97	602	<1	53	480	29	1.44	<5	5	<10	72	1764	<2	36	<10	5	61
165289	1305264	0.162	7	3.30	18	422	<2	8	0.42	<4	6	35	10	1.06	0.51	10	0.81	473	1	59	430	35	0.89	<5	<5	<10	53	1579	6	28	<10	4	55
165290	1305265	0.044	<1	1.82	11	265	<2	2	0.36	<4	4	58	8	0.74	0.06	8	0.46	385	7	106	369	20	0.40	<5	<5	<10	43	1279	<2	26	<10	3	31
165291	1305266	0.702	13	1.68	15	322	<2	<1	<0.01	<4	4	25	11	0.60	0.46	5	0.41	250	<1	43	336	190	0.54	6	<5	<10	29	1133	5	20	<10	3	254
165292D	1305266	0.632	14	1.76	16	335	<2	2	<0.01	<4	4	28	11	0.62	0.20	5	0.42	253	<1	46	349	189	0.53	5	<5	<10	25	1171	<2	21	<10	3	259
165293	1305267	0.087	<1	3.17	10	384	<2	<1	<0.01	<4	3	34	6	0.63	0.14	6	0.43	210	1	53	357	40	0.53	<5	<5	<10	36	1226	<2	21	<10	4	89
165294	1305268	0.053	<1	1.94	14	241	<2	<1	<0.01	<4	3	36	26	0.80	0.17	5	0.50	321	<1	60	355	91	0.68	<5	<5	<10	29	1105	<2	21	<10	3	140
165295	1305269	0.124	<1	2.43	13	203	<2	<1	0.36	<4	3	39	6	1.10	0.24	9	0.90	686	2	67	374	82	0.93	<5	<5	<10	44	1224	3	22	<10	4	77
165296	1305270	5.116	68	0.42	39	248	<2	<1	1.00	21	13	30	50	3.08	0.03	3	0.74	478	<1	23	491	590	0.46	33	<5	229	140	1590	5	84	48	11	1860
165297	1305271	0.661	46	3.14	28	269	<2	<1	0.15	<4	4	13	35	0.83	0.14	7	0.37	226	<1	17	397	77	0.87	12	<5	<10	49	1297	<2	25	<10	4	376
165298	1305272	0.132	2	2.26	13	236	<2	<1	0.32	<4	3	11	7	0.87	0.42	7	0.54	361	<1	16	343	34	0.88	<5	<5	<10	62	1095	<2	21	<10	3	53
165299	1305273	0.076	<1	2.84	11	244	<2	<1	1.02	<4	3	15	12	1.02	0.18	11	0.91	694	<1	27	364	22	0.84	<5	<5	<10	82	1203	8	21	<10	4	49

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, July 15, 2012

Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/11/2012
 Date Completed: 06/22/2012
 Job #: 201242024
 Reference: TL 12257
 Sample #: 95

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
165300	1305274	0.024	<1	2.66	10	233	<2	2	1.10	<4	4	16	10	1.21	0.13	14	1.16	597	<1	34	390	16	1.05	<5	<5	<10	166	1168	5	25	<10	4	51
165301	1305275	0.018	<1	2.95	5	255	<2	<1	0.67	<4	12	17	13	1.27	0.33	9	0.71	108	<1	33	432	13	1.34	5	<5	<10	152	1004	<2	32	<10	4	399
165302	1305276	0.016	<1	1.75	2	205	<2	<1	0.36	<4	10	12	12	1.21	0.50	7	0.67	<100	<1	27	397	12	1.31	<5	<5	<10	102	889	3	28	<10	4	362
165303D	1305276	0.022	<1	1.80	5	215	<2	<1	0.33	<4	11	12	12	1.22	0.28	8	0.68	<100	<1	26	413	9	1.32	<5	<5	<10	96	922	5	30	<10	4	372
165304	1305277	0.012	<1	1.35	7	136	<2	3	1.02	<4	4	21	25	1.11	0.13	8	0.56	145	<1	31	526	46	0.95	<5	<5	<10	118	1256	3	27	<10	5	208
165305	1305278	0.014	<1	2.80	4	139	<2	6	2.17	<4	5	19	1	1.27	0.09	34	1.14	354	<1	24	473	14	0.95	<5	<5	<10	87	1585	10	34	<10	5	13
165306	1305279	0.015	<1	2.17	16	96	<2	7	2.26	<4	3	26	36	0.98	0.05	21	0.80	299	<1	33	335	16	0.67	5	<5	<10	70	1277	8	22	<10	4	22
165307	1305280	<0.005	<1	1.99	<2	225	<2	<1	1.98	<4	15	50	22	3.34	0.05	6	1.26	646	<1	30	576	7	0.16	<5	<5	<10	184	2402	7	110	16	15	54
165308	1305281	<0.005	<1	2.51	8	220	<2	<1	1.22	<4	5	18	2	1.57	0.07	23	0.89	235	<1	29	428	12	1.41	<5	5	<10	112	1383	<2	31	<10	5	32
165309	1305282	<0.005	<1	3.80	3	349	<2	<1	2.04	<4	5	22	9	2.31	0.20	14	1.14	417	<1	35	465	15	2.17	<5	<5	<10	226	1567	<2	36	<10	6	56
165310	1305283	0.006	<1	2.78	4	262	<2	<1	1.29	<4	4	14	5	2.02	0.28	12	0.77	264	<1	23	414	13	2.05	<5	<5	<10	186	1268	<2	31	<10	5	40
165311	1305284	0.296	<1	1.87	3	200	<2	<1	1.01	<4	10	19	17	1.28	0.19	5	0.55	<100	<1	33	502	17	0.95	<5	<5	<10	200	1013	2	19	<10	4	160
165312	1305285	<0.005	<1	4.67	8	278	<2	4	1.40	<4	9	15	8	1.64	0.16	16	0.71	115	<1	31	406	13	1.75	<5	<5	<10	289	1238	2	37	<10	5	119
165313	1305286	0.015	<1	2.81	12	409	<2	2	0.80	<4	12	46	21	2.00	0.13	18	0.66	209	<1	46	468	19	2.18	<5	<5	<10	148	1675	<2	48	<10	7	83
165314D	1305286	0.011	<1	2.89	11	399	<2	4	0.93	<4	12	43	21	1.96	0.08	17	0.66	211	<1	42	461	20	2.14	<5	<5	<10	182	1647	<2	47	<10	7	73
165315	1305287	0.008	<1	2.79	19	440	<2	<1	0.86	<4	9	21	14	1.59	0.05	19	0.80	449	<1	31	589	12	1.18	<5	<5	<10	138	1644	<2	37	<10	7	32
165316	1305288	0.008	<1	4.44	10	503	<2	5	0.87	<4	7	12	7	1.18	0.04	17	0.59	330	<1	26	580	11	0.78	<5	<5	<10	229	1425	3	36	<10	5	15
165317	1305289	0.008	<1	6.92	24	554	<2	8	1.49	<4	8	21	9	1.69	0.08	20	0.67	595	<1	23	521	21	1.37	<5	<5	<10	221	1895	2	37	<10	7	61
165318	1305290	1.913	<1	5.16	4	370	<2	<1	2.17	<4	15	53	30	3.57	0.09	10	1.23	676	<1	30	578	9	0.25	<5	<5	<10	249	2700	15	114	25	16	63
165319	1305291	0.016	<1	6.53	33	581	<2	<1	0.75	<4	8	18	4	2.02	<0.01	13	0.47	517	<1	22	533	17	2.03	<5	<5	<10	135	2046	<2	39	<10	7	51

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, July 15, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/11/2012
 Date Completed: 06/22/2012
 Job #: 201242024
 Reference: TL 12257
 Sample #: 95

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
165320	1305292	0.010	<1	6.82	35	483	<2	<1	2.77	<4	9	22	5	1.81	<0.01	20	1.10	999	<1	27	558	21	1.54	<5	6	<10	183	1763	3	37	<10	7	55
165321	1305293	0.010	<1	3.88	35	257	<2	<1	2.57	<4	7	13	2	1.74	<0.01	8	0.64	900	<1	23	532	15	1.71	<5	<5	<10	166	1413	8	31	<10	5	40
165322	1305294	0.057	<1	6.74	16	439	<2	7	1.20	<4	21	141	79	3.56	<0.01	17	1.05	469	<1	76	519	173	1.36	<5	5	<10	139	2279	<2	96	<10	11	413
165323	1305295	0.046	<1	7.02	30	337	<2	4	2.26	<4	18	97	54	3.63	0.04	17	1.21	998	<1	60	423	89	1.87	<5	<5	<10	157	1997	5	66	<10	12	128
165324	1305296	0.047	<1	7.79	34	433	2	<1	2.35	<4	20	112	44	3.68	0.02	19	1.26	1015	1	63	516	98	1.87	7	<5	<10	170	2134	<2	73	<10	13	120
165325R	1305296	0.046	<1	7.70	36	424	2	6	2.36	<4	19	113	45	3.55	0.13	18	1.21	995	1	65	491	99	1.80	<5	<5	<10	174	2081	5	74	<10	13	117
165326	1305297	0.103	<1	6.66	31	348	<2	3	1.46	<4	13	68	41	2.58	0.03	14	0.91	507	<1	41	497	50	1.68	5	<5	<10	96	1910	<2	54	<10	9	90
165327	1305298	0.100	<1	5.98	40	305	<2	<1	0.52	<4	8	24	9	1.82	0.06	8	0.38	181	<1	24	492	31	1.79	<5	<5	<10	65	1794	<2	38	<10	7	67
165328	1305299	0.035	<1	6.79	37	347	<2	5	1.65	<4	8	26	5	2.03	0.11	14	0.86	402	<1	26	513	33	1.54	<5	<5	<10	82	1915	2	39	<10	7	43
165329	1305300	<0.005	<1	6.59	7	420	<2	<1	2.65	<4	18	63	24	3.67	0.39	12	1.36	733	<1	31	630	8	0.29	<5	<5	<10	298	3265	<2	125	27	18	59
165330	1305301	0.014	<1	8.64	24	381	<2	13	2.93	<4	9	31	9	2.06	0.03	21	1.38	641	<1	29	529	26	0.95	5	7	<10	103	2285	<2	44	<10	8	75
165331	1305302	0.008	<1	7.99	43	493	2	<1	2.46	<4	8	27	8	2.05	0.09	17	1.06	483	<1	26	505	31	1.26	<5	<5	<10	105	2163	12	42	<10	7	62
165332	1305303	0.020	<1	7.81	53	522	2	2	2.43	<4	9	34	13	1.96	0.12	17	1.13	596	3	40	528	45	0.96	<5	<5	<10	92	2237	<2	44	<10	7	87
165333	1305304	0.044	<1	8.02	43	497	2	5	1.78	<4	12	74	56	2.24	0.14	16	1.08	578	5	64	533	82	1.31	<5	<5	<10	70	1935	<2	58	<10	8	84
165334	1305305	0.108	<1	8.09	183	622	2	3	0.62	<4	28	171	180	4.42	0.16	11	0.67	258	5	126	566	125	4.09	5	<5	<10	66	1809	8	118	<10	10	136
165335	1305306	1.565	6	5.66	229	537	2	9	0.10	6	11	73	97	2.24	0.41	7	0.22	<100	6	74	411	393	2.42	35	<5	<10	50	1299	<2	58	24	6	1495
165336D	1305306	1.536	6	6.83	240	549	2	8	0.11	6	11	78	97	2.26	0.17	7	0.23	<100	5	69	451	394	2.44	34	8	<10	51	1304	<2	58	24	7	1498
165337	1305307	0.014	<1	7.71	49	553	2	6	0.21	<4	8	43	15	1.28	0.24	7	0.30	<100	5	53	511	66	1.22	<5	6	<10	61	1441	<2	40	11	7	127
165338	1305308	0.013	<1	8.22	51	544	2	<1	0.29	<4	12	80	22	1.57	0.16	9	0.35	117	5	68	563	40	1.41	<5	10	<10	59	2007	2	62	11	9	87
165339	1305309	0.058	<1	5.44	25	322	<2	<1	1.17	<4	17	151	43	2.45	0.02	9	0.92	390	2	87	478	31	1.13	<5	5	<10	66	2169	2	77	<10	13	38

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, July 15, 2012

Final Certificate

Treasury Metals Inc
Exchange Tower 130 King St Suite 3680
Toronto, On, CAN
M5X 1B1
Ph#: (416) 599-4133
Fax#: (416) 599-4959
Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 06/11/2012
Date Completed: 06/22/2012
Job #: 201242024
Reference: TL 12257
Sample #: 95

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
165340	1305310	0.239	<1	<0.01	321	>5000	<2	<1	0.46	<4	5	13	22	2.14	<0.01	<1	0.05	<100	3	13	<100	14	0.40	12	<5	<10	61	542	<2	12	34	5	13
165341	1305311	0.046	<1	6.44	26	314	<2	2	1.98	<4	16	152	57	3.10	0.06	10	1.25	584	5	91	409	45	1.43	<5	<5	<10	99	1669	12	71	10	13	83
165342	1305312	0.241	<1	6.36	86	364	2	7	0.13	<4	20	141	70	2.64	0.54	6	0.22	<100	5	95	467	74	2.44	<5	<5	<10	50	1864	2	90	15	9	398
165343	1305313	0.393	<1	5.82	95	341	2	<1	0.15	<4	21	150	66	2.75	0.52	9	0.33	120	6	114	506	95	2.72	<5	<5	<10	55	1845	<2	104	10	9	181
165344	1305314	0.194	<1	6.76	21	269	2	3	1.49	<4	19	147	47	3.25	0.25	13	1.15	551	4	83	497	55	1.62	6	<5	<10	101	1991	10	75	<10	14	67
165345	1305315	0.402	<1	3.68	91	253	<2	4	0.21	4	16	105	37	2.80	0.58	4	0.49	183	<1	66	520	249	2.70	<5	<5	<10	46	1601	<2	66	16	10	831
165346	1305316	0.430	<1	5.96	85	322	2	<1	0.49	5	17	117	46	2.96	0.46	10	0.58	231	4	73	447	400	2.84	6	<5	<10	54	1833	6	71	20	10	1209
165347D	1305316	0.494	<1	6.22	81	323	2	2	0.50	5	17	124	47	2.97	0.70	11	0.60	234	5	83	449	403	2.83	5	<5	<10	54	1863	<2	72	18	11	1191
165348	1305317	0.322	<1	7.73	8	405	2	<1	1.38	<4	19	163	63	3.31	0.12	13	1.07	465	4	90	550	61	1.87	<5	<5	<10	103	2018	<2	84	<10	16	284
165349	1305318	0.240	<1	6.04	51	365	2	11	0.21	<4	7	73	47	1.56	0.08	6	0.20	<100	6	60	333	173	1.40	12	<5	<10	57	1349	7	38	<10	8	145
165350	1305319	1.394	6	6.25	161	400	2	<1	0.58	<4	7	61	176	1.95	0.01	8	0.49	173	10	79	410	686	1.92	103	5	<10	80	1411	<2	35	15	7	465
165351	1305320	0.006	<1	6.12	4	386	<2	2	2.45	<4	16	59	23	3.33	0.14	11	1.24	665	<1	29	571	12	0.29	<5	<5	<10	278	2960	<2	116	24	17	52
165352	1305321	0.975	1	5.02	121	386	<2	<1	0.08	<4	6	43	63	1.89	0.56	5	0.19	<100	5	51	352	184	2.06	19	<5	<10	56	1360	3	32	16	5	651
165353	1305322	0.073	<1	6.73	27	468	2	7	1.60	<4	7	50	29	1.94	0.12	11	1.02	567	6	67	460	39	1.34	<5	6	<10	112	1549	9	35	<10	7	120
165354	1305323	0.080	<1	5.01	20	424	<2	<1	0.69	<4	7	46	18	1.56	0.66	7	0.57	211	8	60	375	22	1.22	<5	5	<10	56	1541	<2	35	<10	6	75
165355	1305324	0.040	<1	5.02	20	332	2	4	3.54	<4	7	42	26	2.29	0.37	14	1.70	825	3	46	391	28	1.00	<5	7	<10	131	2003	14	43	<10	5	96
165356	1305325	0.582	5	6.80	94	418	2	<1	1.37	5	14	92	61	2.95	0.06	14	0.85	457	2	60	451	1130	2.69	9	8	<10	101	2206	<2	59	22	10	1419
165357	1305326	0.092	<1	3.54	11	144	<2	<1	0.93	<4	9	80	25	1.64	0.02	9	0.59	324	3	49	248	41	0.55	<5	<5	<10	70	1375	4	38	<10	8	50
165358D	1305326	0.086	<1	2.22	12	108	<2	<1	0.89	<4	11	101	29	1.88	<0.01	4	0.68	369	<1	63	293	41	0.61	<5	<5	<10	82	1386	<2	46	<10	9	51
165359	1305327	0.205	<1	6.61	59	314	2	<1	1.61	<4	20	160	45	3.45	0.56	18	1.03	593	6	97	467	66	1.72	<5	<5	<10	139	2912	<2	84	<10	14	95

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
Jason Moore, General Manager

The results included on this report relate only to the items tested.
The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, July 15, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/11/2012
 Date Completed: 06/22/2012
 Job #: 201242024
 Reference: TL 12257
 Sample #: 95

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
165360	1305328	0.032	<1	6.99	4	277	2	<1	1.62	<4	18	149	41	3.42	0.07	22	1.30	605	3	83	452	40	0.74	<5	<5	<10	142	2707	6	77	<10	16	70
165361	1305329	0.029	<1	6.89	<2	290	2	<1	1.74	<4	21	152	45	3.61	0.14	22	1.21	598	3	91	489	33	0.83	<5	5	<10	170	2830	<2	84	<10	16	66
165362	1305330	4.997	68	5.03	36	455	<2	2	1.47	21	15	42	53	3.34	0.66	9	0.79	516	2	26	545	600	0.60	76	<5	244	235	2116	8	95	61	14	1890
165363	1305331	0.148	<1	6.01	24	351	2	<1	1.64	<4	18	142	56	3.29	0.19	17	1.10	587	4	85	458	62	1.30	<5	<5	<10	148	2519	2	76	11	15	200

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 22, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/11/2012
 Date Completed: 06/22/2012
 Job #: 201242024
 Reference: TL 12257
 Sample #: 95

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
165260	1305237	51	0.001	0.051
165261	1305238	403	0.012	0.403
165262	1305239	65	0.002	0.065
165263	1305240	12	<0.001	0.012
165264	1305241	25	<0.001	0.025
165265	1305242	15	<0.001	0.015
165266	1305243	9	<0.001	0.009
165267	1305244	14	<0.001	0.014
165268	1305245	14	<0.001	0.014
165269	1305246	19	<0.001	0.019
165270 Dup	1305246	55	0.002	0.055
165271	1305247	12	<0.001	0.012
165272	1305248	16	<0.001	0.016
165273	1305249	13	<0.001	0.013
165274	1305250	223	0.007	0.223
165275	1305251	82	0.002	0.082
165276	1305252	136	0.004	0.136
165277	1305253	39	0.001	0.039
165278	1305254	36	0.001	0.036
165279	1305255	302	0.009	0.302
165280	1305256	223	0.007	0.223
165281 Dup	1305256	270	0.008	0.270
165282	1305257	266	0.008	0.266
165283	1305258	66	0.002	0.066
165284	1305259	40	0.001	0.040
165285	1305260	8	<0.001	0.008
165286	1305261	480	0.014	0.480
165287	1305262	78	0.002	0.078
165288	1305263	39	0.001	0.039
165289	1305264	162	0.005	0.162

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 22, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/11/2012
 Date Completed: 06/22/2012
 Job #: 201242024
 Reference: TL 12257
 Sample #: 95

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
165290	1305265	44	0.001	0.044
165291	1305266	702	0.020	0.702
165292 Dup	1305266	632	0.018	0.632
165293	1305267	87	0.003	0.087
165294	1305268	53	0.002	0.053
165295	1305269	124	0.004	0.124
165296	1305270	5116	0.149	5.116
165297	1305271	661	0.019	0.661
165298	1305272	132	0.004	0.132
165299	1305273	76	0.002	0.076
165300	1305274	24	<0.001	0.024
165301	1305275	18	<0.001	0.018
165302	1305276	16	<0.001	0.016
165303 Dup	1305276	22	<0.001	0.022
165304	1305277	12	<0.001	0.012
165305	1305278	14	<0.001	0.014
165306	1305279	15	<0.001	0.015
165307	1305280	<5	<0.001	<0.005
165308	1305281	<5	<0.001	<0.005
165309	1305282	<5	<0.001	<0.005
165310	1305283	6	<0.001	0.006
165311	1305284	296	0.009	0.296
165312	1305285	<5	<0.001	<0.005
165313	1305286	15	<0.001	0.015
165314 Dup	1305286	11	<0.001	0.011
165315	1305287	8	<0.001	0.008
165316	1305288	8	<0.001	0.008
165317	1305289	8	<0.001	0.008
165318	1305290	1913	0.056	1.913
165319	1305291	16	<0.001	0.016

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H Bsc., Laboratory Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 22, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/11/2012
 Date Completed: 06/22/2012
 Job #: 201242024
 Reference: TL 12257
 Sample #: 95

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
165320	1305292	10	<0.001	0.010
165321	1305293	10	<0.001	0.010
165322	1305294	57	0.002	0.057
165323	1305295	46	0.001	0.046
165324	1305296	47	0.001	0.047
165325 Rep	1305296	46	0.001	0.046
165326	1305297	103	0.003	0.103
165327	1305298	100	0.003	0.100
165328	1305299	35	0.001	0.035
165329	1305300	<5	<0.001	<0.005
165330	1305301	14	<0.001	0.014
165331	1305302	8	<0.001	0.008
165332	1305303	20	<0.001	0.020
165333	1305304	44	0.001	0.044
165334	1305305	108	0.003	0.108
165335	1305306	1565	0.046	1.565
165336 Dup	1305306	1536	0.045	1.536
165337	1305307	14	<0.001	0.014
165338	1305308	13	<0.001	0.013
165339	1305309	58	0.002	0.058
165340	1305310	239	0.007	0.239
165341	1305311	46	0.001	0.046
165342	1305312	241	0.007	0.241
165343	1305313	393	0.011	0.393
165344	1305314	194	0.006	0.194
165345	1305315	402	0.012	0.402
165346	1305316	430	0.013	0.430
165347 Dup	1305316	494	0.014	0.494
165348	1305317	322	0.009	0.322
165349	1305318	240	0.007	0.240

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 22, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/11/2012
 Date Completed: 06/22/2012
 Job #: 201242024
 Reference: TL 12257
 Sample #: 95

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
165350	1305319	1394	0.041	1.394
165351	1305320	6	<0.001	0.006
165352	1305321	975	0.028	0.975
165353	1305322	73	0.002	0.073
165354	1305323	80	0.002	0.080
165355	1305324	40	0.001	0.040
165356	1305325	582	0.017	0.582
165357	1305326	92	0.003	0.092
165358 Dup	1305326	86	0.003	0.086
165359	1305327	205	0.006	0.205
165360	1305328	32	<0.001	0.032
165361	1305329	29	<0.001	0.029
165362	1305330	4997	0.146	4.997
165363	1305331	148	0.004	0.148

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianliuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.

The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, July 15, 2012

Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/11/2012
 Date Completed: 06/22/2012
 Job #: 201242025
 Reference: TL 12258
 Sample #: 127

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
165364	1305332	0.083	4	6.97	20	1746	<2	3	2.32	16	15	23	88	2.66	<0.01	23	1.20	855	17	40	618	3271	1.77	<5	<5	<10	232	3524	9	60	45	10	4004
165365	1305333	0.026	<1	6.38	20	1555	<2	4	2.21	<4	15	43	25	2.80	<0.01	23	1.12	791	17	58	622	64	1.13	<5	<5	<10	216	3436	6	64	<10	9	154
165366	1305334	0.087	<1	4.99	35	1306	<2	1	1.68	5	14	26	22	2.80	<0.01	18	1.00	698	15	43	552	880	1.98	<5	<5	<10	178	3041	<2	54	12	8	874
165367	1305335	0.026	<1	5.14	3	1503	<2	<1	1.55	<4	11	31	31	2.09	0.06	18	0.83	638	16	45	530	53	0.89	<5	<5	<10	169	3056	<2	52	<10	8	79
165368	1305336	0.027	<1	3.88	4	1329	<2	<1	1.21	<4	9	30	26	1.85	<0.01	15	0.76	585	14	41	472	34	0.72	<5	<5	<10	139	2811	<2	48	<10	7	62
165369	1305337	0.068	<1	5.26	14	1429	<2	<1	1.54	<4	11	17	52	2.11	<0.01	19	0.93	750	12	32	585	62	1.17	<5	8	<10	175	3203	4	52	10	8	284
165370	1305338	0.038	<1	4.84	4	1281	<2	<1	1.38	<4	20	129	41	3.20	<0.01	24	1.24	684	13	79	420	23	0.98	<5	<5	<10	134	3376	<2	79	<10	13	213
165371	1305339	0.031	<1	3.91	15	430	<2	<1	0.37	<4	9	33	15	1.00	<0.01	9	0.41	149	<1	35	232	20	0.84	<5	<5	<10	88	1588	<2	33	<10	5	95
165372	1305340	0.011	<1	3.91	<2	1042	<2	2	2.21	<4	16	48	22	3.27	<0.01	12	1.33	630	7	31	551	6	0.20	<5	<5	<10	261	3176	<2	114	17	16	56
165373	1305341	0.009	<1	4.32	4	1118	<2	<1	1.18	<4	7	17	6	0.62	<0.01	11	0.47	125	10	29	228	8	0.48	<5	5	<10	139	2199	<2	32	<10	6	17
165374D	1305341	0.005	<1	4.84	3	1243	<2	<1	1.24	<4	7	20	6	0.62	0.04	13	0.49	125	13	31	242	11	0.51	<5	<5	<10	143	2360	5	32	<10	6	17
165375	1305342	0.008	<1	5.34	5	1278	<2	6	0.89	<4	7	15	3	0.68	0.12	18	0.72	221	12	28	249	12	0.50	<5	<5	<10	151	2426	5	33	<10	6	23
165376	1305343	0.011	<1	4.38	4	1167	<2	4	0.78	<4	7	18	6	0.79	<0.01	15	0.58	186	12	30	222	12	0.58	<5	<5	<10	141	2269	4	32	<10	6	20
165377	1305344	0.017	<1	4.86	11	408	<2	4	0.73	<4	6	22	21	0.54	<0.01	8	0.21	123	<1	36	366	65	0.41	<5	<5	<10	148	1554	<2	28	<10	4	148
165378	1305345	0.010	<1	3.85	3	1088	<2	4	0.81	<4	6	15	8	0.43	0.03	12	0.32	124	9	24	354	33	0.29	<5	<5	<10	153	2151	<2	31	<10	5	25
165379	1305346	0.009	<1	4.89	<2	1134	<2	<1	1.17	<4	6	13	14	0.57	0.02	13	0.34	149	10	24	381	27	0.34	<5	<5	<10	188	2229	<2	31	<10	6	18
165380	1305347	0.012	<1	5.53	6	1179	<2	3	1.59	<4	6	13	7	0.44	0.21	12	0.33	150	9	26	335	15	0.28	<5	<5	<10	235	2076	<2	31	<10	5	24
165381	1305348	0.012	<1	4.15	2	1235	<2	<1	1.07	<4	5	19	6	0.61	0.11	14	0.43	173	11	29	308	38	0.35	<5	<5	<10	182	2026	3	30	<10	5	39
165382	1305349	0.057	<1	4.21	11	1305	<2	<1	1.05	<4	8	13	53	1.36	0.07	17	0.62	355	13	26	417	146	0.76	<5	<5	<10	191	2494	2	38	<10	7	176
165383	1305350	1.930	<1	4.18	7	1194	<2	<1	2.17	<4	17	49	31	3.77	0.03	15	1.43	686	11	35	593	8	0.21	<5	<5	<10	242	3416	6	123	21	17	63

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, July 15, 2012

Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 06/11/2012
 Date Completed: 06/22/2012
 Job #: 201242025
 Reference: TL 12258
 Sample #: 127

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
165384	1305351	0.076	<1	5.19	9	1292	<2	<1	1.17	<4	9	17	23	1.72	0.06	24	0.59	314	12	31	464	30	0.84	<5	<5	<10	256	2778	5	41	<10	8	67
165385D	1305351	0.079	<1	5.04	6	1288	<2	<1	1.13	<4	9	19	23	1.70	<0.01	24	0.59	312	12	34	467	26	0.81	<5	<5	<10	249	2779	<2	40	<10	8	67
165386	1305352	0.201	<1	6.32	5	1350	<2	5	1.70	<4	11	22	49	2.10	0.03	20	0.56	366	13	41	549	30	1.09	<5	<5	<10	283	2889	<2	44	<10	9	87
165387	1305353	0.015	<1	6.08	3	1417	<2	3	1.72	<4	10	11	25	2.09	0.04	20	0.66	523	9	26	618	33	0.80	<5	5	<10	249	2941	5	48	<10	9	48
165388	1305354	0.041	<1	5.41	<2	1391	<2	<1	1.31	<4	9	15	24	1.98	<0.01	17	0.57	517	14	27	445	26	0.85	<5	<5	<10	194	2909	3	41	<10	8	90
165389	1305355	0.013	<1	5.49	2	1239	<2	<1	1.87	<4	8	12	44	1.80	0.08	14	0.63	612	10	23	444	171	0.62	<5	<5	<10	211	2701	<2	41	<10	8	384
165390	1305356	0.024	<1	4.16	<2	1294	<2	2	1.36	<4	9	14	51	1.85	0.09	16	0.67	594	14	22	456	174	0.70	<5	7	<10	140	2844	<2	39	12	9	442
165391	1305357	0.020	<1	5.17	6	1387	<2	<1	1.76	<4	9	15	24	1.94	0.05	20	0.91	693	14	26	442	42	0.79	<5	<5	<10	165	2753	<2	38	<10	8	134
165392	1305358	0.022	<1	5.21	<2	1147	<2	5	1.53	<4	10	12	18	1.49	0.22	14	0.51	562	7	27	443	29	0.70	<5	5	<10	154	2544	<2	41	<10	7	172
165393	1305359	0.062	<1	5.53	23	1400	<2	<1	1.80	<4	10	16	23	1.68	0.07	19	0.95	720	14	29	428	214	1.06	<5	<5	<10	150	2715	5	37	<10	8	292
165394	1305360	0.009	<1	4.16	2	1202	<2	4	2.23	<4	16	48	21	3.30	<0.01	14	1.36	645	11	30	569	6	0.22	<5	<5	<10	249	3552	2	115	19	17	55
165395	1305361	0.023	<1	5.39	19	1345	<2	<1	1.73	<4	8	24	20	1.70	<0.01	17	0.91	681	13	27	428	64	0.92	<5	<5	<10	148	2668	4	37	<10	8	325
165396D	1305361	0.027	<1	5.52	17	1372	<2	<1	1.78	<4	9	23	21	1.72	<0.01	18	0.92	690	13	28	442	65	0.94	<5	<5	<10	152	2697	5	37	<10	8	329
165397	1305362	0.026	<1	5.28	21	1360	<2	<1	1.39	<4	10	16	20	1.57	<0.01	18	0.65	549	15	32	450	19	0.83	<5	6	<10	149	2769	<2	38	10	8	381
165398	1305363	0.027	<1	5.24	8	1308	<2	3	2.65	<4	9	19	29	1.66	0.06	13	0.64	658	12	31	437	16	0.71	<5	<5	<10	200	2630	<2	39	<10	9	90
165399	1305364	0.021	<1	4.72	7	1241	<2	<1	1.35	<4	9	14	17	0.93	0.06	12	0.42	321	13	28	396	15	0.48	<5	<5	<10	148	2382	<2	35	<10	8	38
165400	1305365	0.018	<1	5.41	12	1392	<2	4	0.75	<4	8	17	17	1.16	0.10	17	0.52	293	14	28	438	14	0.75	<5	8	<10	124	2814	3	38	<10	7	128
165401	1305366	0.011	<1	4.37	5	1238	<2	1	1.32	<4	9	20	30	1.83	0.05	15	0.78	340	15	35	444	30	1.20	<5	<5	<10	128	2513	2	35	<10	8	108
165402	1305367	0.259	9	5.46	20	1271	<2	5	1.25	<4	10	17	38	0.81	0.21	17	1.04	675	15	32	289	518	0.75	15	<5	<10	123	2345	4	32	13	6	820
165403	1305368	0.061	<1	4.45	16	1276	<2	<1	0.69	<4	12	34	9	0.96	0.08	19	0.99	598	19	60	320	92	0.81	<5	<5	<10	78	2199	4	29	<10	6	236

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, July 15, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/11/2012
 Date Completed: 06/22/2012
 Job #: 201242025
 Reference: TL 12258
 Sample #: 127

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
165404	1305369	0.326	3	5.55	33	1290	<2	<1	0.11	<4	11	77	45	1.32	0.21	14	0.45	108	30	135	307	195	1.00	6	<5	<10	69	2388	<2	34	<10	6	186
165405	1305370	0.221	<1	0.55	448	>5000	<2	3	0.99	<4	10	16	31	3.06	0.01	8	0.26	<100	28	17	<100	23	0.76	19	6	<10	159	2230	4	24	56	10	26
165406	1305371	0.561	<1	5.28	35	1345	<2	2	0.07	<4	9	80	24	1.60	0.08	13	0.41	<100	30	135	283	57	1.34	7	<5	<10	74	2258	<2	34	<10	6	70
165407D	1305371	0.575	<1	4.77	40	1258	<2	4	0.06	<4	10	90	25	1.68	0.22	11	0.39	<100	33	157	297	57	1.35	8	<5	<10	69	2143	<2	33	<10	6	74
165408	1305372	1.536	1	5.27	28	1406	<2	<1	0.13	<4	7	55	20	1.23	0.26	14	0.45	<100	27	89	307	110	1.12	6	<5	<10	76	2300	<2	33	<10	7	359
165409	1305373	0.295	1	6.71	27	1513	<2	5	0.76	<4	7	89	21	1.82	0.07	18	0.83	439	33	146	448	153	1.45	<5	<5	<10	111	2566	<2	44	<10	8	367
165410	1305374	0.140	<1	4.28	13	1038	<2	<1	1.30	<4	5	65	33	1.68	0.05	12	1.14	629	19	116	437	152	1.13	<5	<5	<10	106	2056	2	36	<10	6	284
165411	1305375	0.054	<1	6.01	28	1394	<2	4	1.29	<4	6	38	24	2.32	0.04	18	1.09	581	19	68	480	35	2.11	<5	<5	<10	113	2558	10	43	<10	7	169
165412	1305376	0.063	<1	7.81	27	1674	2	<1	1.37	<4	7	59	18	2.46	0.04	23	1.13	670	25	100	508	41	2.12	<5	<5	<10	124	3071	3	54	<10	8	237
165413	1305377	0.090	1	6.82	11	1628	<2	8	0.12	<4	5	38	19	0.86	0.11	15	0.51	105	21	65	315	167	0.73	6	<5	<10	81	2657	<2	40	11	7	599
165414	1305378	0.486	6	5.93	50	1415	<2	2	0.09	<4	7	66	133	1.22	0.24	12	0.45	105	26	110	251	795	1.02	37	<5	<10	85	2404	<2	35	14	6	803
165415	1305379	0.202	<1	6.06	12	1368	<2	8	0.23	<4	5	50	16	0.92	0.22	14	0.53	182	23	84	343	75	0.73	<5	<5	<10	88	2478	<2	35	<10	6	241
165416	1305380	0.005	<1	5.15	2	1225	<2	<1	2.49	<4	17	53	23	3.56	0.20	14	1.44	708	11	33	593	6	0.21	<5	6	<10	304	3968	4	125	22	18	58
165417	1305381	0.455	<1	6.19	16	1402	2	<1	0.52	<4	5	37	11	1.01	0.34	15	0.58	231	21	53	334	59	0.95	<5	5	<10	98	2499	<2	34	<10	7	433
165418D	1305381	0.469	<1	6.20	16	1398	<2	<1	0.52	<4	5	46	12	1.02	0.25	15	0.56	229	23	72	324	62	0.91	<5	<5	<10	98	2472	<2	34	10	7	420
165419	1305382	0.034	<1	7.32	13	1462	<2	3	1.38	<4	5	39	6	1.03	0.28	22	0.96	615	24	69	382	35	0.81	<5	<5	<10	140	2728	3	38	<10	7	47
165420	1305383	0.066	<1	6.57	7	1516	<2	7	0.93	<4	5	38	5	0.71	0.19	21	0.58	317	24	63	380	32	0.52	<5	6	<10	114	2667	3	38	<10	8	21
165421	1305384	0.995	14	7.28	15	1641	<2	5	1.01	<4	5	40	23	0.93	0.08	26	0.69	338	27	64	387	160	0.74	5	<5	<10	136	2856	2	38	<10	8	196
165422	1305385	0.121	1	6.72	15	1571	<2	8	1.53	<4	8	40	34	1.54	0.02	26	1.01	560	27	68	376	43	1.41	<5	<5	<10	184	2806	5	39	<10	8	110
165423	1305386	0.011	<1	3.03	4	1342	<2	<1	1.19	<4	6	56	17	0.92	0.03	12	0.51	153	28	81	111	8	0.80	<5	<5	<10	128	2033	8	24	<10	7	69

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, July 15, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/11/2012
 Date Completed: 06/22/2012
 Job #: 201242025
 Reference: TL 12258
 Sample #: 127

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
165424	1305387	0.017	<1	8.02	4	1615	2	2	1.95	<4	11	33	14	1.94	0.28	28	1.04	227	24	58	427	14	2.06	<5	<5	<10	266	2761	10	44	<10	9	50
165425	1305388	0.009	<1	7.69	4	1464	<2	8	2.00	<4	7	32	10	2.24	0.30	29	1.30	282	21	58	485	12	2.36	<5	<5	<10	296	2433	3	47	<10	9	59
165426	1305389	0.009	<1	4.97	3	1102	<2	2	1.49	<4	5	33	5	2.13	<0.01	18	0.74	246	16	63	385	14	2.23	<5	<5	<10	238	1830	2	38	<10	7	53
165427	1305390	5.436	73	4.48	37	1437	<2	<1	1.52	22	16	34	54	3.56	0.29	14	0.96	520	17	29	532	620	0.61	68	<5	246	256	3025	<2	103	63	16	1949
165428	1305391	0.013	<1	5.89	10	984	<2	5	1.95	<4	7	41	16	2.97	0.02	22	1.03	365	22	69	406	15	3.05	<5	<5	<10	249	2249	3	43	<10	10	78
165429R	1305391	0.012	<1	6.78	12	1337	<2	<1	2.40	<4	7	30	12	2.92	0.35	21	1.07	384	19	49	415	15	3.06	<5	<5	<10	315	2203	<2	42	<10	9	129
165430	1305392	0.012	<1	5.22	5	1100	<2	<1	1.86	<4	7	47	8	2.31	0.13	21	0.97	268	18	89	443	11	1.96	<5	<5	<10	270	1813	2	45	<10	8	76
165431	1305393	0.013	<1	5.93	7	1075	<2	2	2.71	<4	8	15	12	2.56	0.22	26	1.52	371	9	26	435	16	2.22	<5	<5	<10	344	2457	<2	43	<10	8	72
165432	1305394	0.012	<1	5.28	<2	1051	<2	<1	1.99	<4	6	17	9	2.49	0.03	23	1.24	219	10	33	439	15	2.67	<5	<5	<10	304	2085	4	40	<10	8	52
165433	1305395	0.010	<1	5.21	3	1050	<2	<1	1.60	<4	8	17	18	1.55	0.26	22	0.82	187	8	30	452	11	1.69	<5	7	<10	259	2376	3	43	<10	7	41
165434	1305396	0.009	<1	4.84	<2	1068	<2	<1	1.45	<4	8	14	21	1.50	0.02	23	0.83	186	8	28	452	9	1.62	<5	<5	<10	235	2393	<2	42	<10	7	35
165435	1305397	<0.005	<1	3.71	9	902	<2	<1	1.48	<4	9	53	10	1.85	0.07	15	0.42	159	17	106	391	23	1.80	<5	6	<10	203	2026	<2	35	<10	6	40
165436	1305398	0.007	<1	3.55	5	850	<2	3	1.86	<4	8	53	9	1.77	0.02	12	0.44	218	15	88	377	23	1.57	<5	<5	<10	467	2099	<2	29	10	6	35
165437	1305399	0.007	<1	3.65	12	888	<2	<1	0.93	<4	7	22	15	1.52	0.11	19	0.64	365	8	34	349	15	1.19	<5	<5	<10	247	2088	<2	31	<10	6	39
165438	1305400	<0.005	<1	3.12	<2	922	<2	6	2.17	<4	16	48	22	3.39	0.14	11	1.37	649	5	33	574	7	0.18	<5	<5	<10	240	3107	11	116	22	16	57
165439	1305401	0.017	<1	3.71	18	1004	<2	6	0.67	<4	11	78	22	2.12	0.09	20	0.55	316	21	123	391	16	1.72	<5	<5	<10	232	2180	<2	44	<10	7	32
165440D	1305401	0.013	<1	3.58	17	1020	<2	<1	0.64	<4	11	81	15	2.14	0.08	21	0.55	315	22	130	399	20	1.77	<5	<5	<10	221	2217	8	44	<10	7	33
165441	1305402	<0.005	<1	3.52	8	953	<2	<1	0.80	<4	10	65	14	2.31	0.08	21	0.57	375	18	100	501	11	1.83	<5	<5	<10	253	2175	<2	43	<10	7	32
165442	1305403	0.006	<1	4.77	42	1190	<2	<1	1.40	<4	10	55	11	2.40	0.10	18	0.86	517	16	88	554	19	1.62	<5	<5	<10	220	2438	<2	45	<10	8	80
165443	1305404	0.018	1	3.33	37	357	<2	<1	0.73	<4	8	75	15	2.01	0.10	7	0.57	593	8	122	474	33	1.48	<5	5	<10	132	1278	<2	35	<10	6	100

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, July 15, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/11/2012
 Date Completed: 06/22/2012
 Job #: 201242025
 Reference: TL 12258
 Sample #: 127

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
165444	1305405	0.020	13	4.27	56	339	<2	<1	<0.01	<4	8	73	27	1.73	0.15	<1	0.15	<100	10	123	553	92	1.49	<5	<5	<10	80	1389	<2	37	<10	6	415
165445	1305406	0.007	<1	3.95	59	347	<2	<1	0.54	<4	8	48	23	1.85	0.15	6	0.41	428	3	77	480	53	1.72	<5	<5	<10	127	1448	<2	37	<10	6	133
165446	1305407	0.010	<1	4.90	47	356	<2	3	2.39	<4	12	80	27	2.62	<0.01	12	0.97	854	4	90	534	34	1.68	5	<5	<10	182	1846	12	50	<10	8	71
165447	1305408	0.008	<1	4.29	30	361	<2	1	1.36	<4	9	34	23	1.77	0.36	14	0.66	555	<1	58	562	33	0.83	<5	5	<10	153	1877	7	36	<10	6	87
165448	1305409	0.010	<1	3.96	21	328	<2	<1	1.13	<4	9	50	5	1.91	0.36	15	0.67	557	5	95	582	19	0.69	<5	<5	<10	157	1935	<2	38	<10	6	67
165449	1305410	1.952	<1	3.37	5	333	<2	6	2.11	<4	16	53	31	3.73	0.24	8	1.32	702	<1	37	599	10	0.19	<5	<5	<10	233	2582	23	119	23	15	60
165450	1305411	0.047	<1	3.49	13	308	<2	<1	0.79	<4	8	37	8	1.90	0.24	15	0.63	529	2	69	575	13	0.65	<5	<5	<10	144	1894	<2	37	<10	6	62
165451D	1305411	0.033	<1	3.69	14	307	<2	<1	0.77	<4	8	25	7	1.79	0.17	15	0.63	523	<1	45	567	9	0.66	<5	5	<10	136	1877	4	36	<10	6	62
165452	1305412	<0.005	<1	3.06	15	326	<2	<1	1.35	<4	9	20	5	1.87	0.13	14	0.81	488	<1	38	557	14	0.63	<5	5	<10	157	1730	<2	34	<10	6	65
165453	1305413	0.009	<1	4.21	6	395	<2	<1	1.53	<4	8	39	5	2.08	0.04	17	0.86	527	2	70	587	19	0.57	<5	<5	<10	150	1802	<2	39	<10	6	63
165454	1305414	0.013	<1	4.59	15	483	<2	2	0.59	<4	9	55	8	2.08	0.12	11	0.44	267	7	103	598	63	1.53	<5	<5	<10	149	1884	<2	38	<10	5	87
165455	1305415	0.361	12	2.11	33	300	<2	7	<0.01	8	7	53	111	1.95	0.08	2	0.18	107	7	101	621	1686	1.86	<5	<5	<10	78	1327	11	29	26	4	2084
165456	1305416	0.283	11	4.44	32	406	<2	<1	0.16	8	8	68	95	2.04	0.15	6	0.22	123	12	121	687	1551	1.86	8	<5	<10	114	1663	<2	36	25	5	2260
165457	1305417	0.007	<1	4.76	<2	385	<2	<1	2.46	<4	9	41	19	2.02	0.16	11	0.93	323	1	69	507	42	0.58	<5	<5	<10	206	1639	3	35	<10	6	66
165458	1305418	0.010	<1	5.26	17	314	<2	<1	2.17	<4	8	35	12	1.88	0.20	14	1.16	419	<1	50	506	25	0.93	<5	<5	<10	132	1704	2	35	<10	6	75
165459	1305419	0.040	<1	4.89	24	286	<2	<1	2.57	<4	12	65	32	2.31	0.18	11	1.37	773	2	72	500	33	1.06	<5	<5	<10	94	1767	6	46	<10	8	117
165460	1305420	<0.005	<1	4.42	2	355	<2	2	2.44	<4	17	57	24	3.62	0.36	9	1.36	710	<1	36	616	9	0.20	5	<5	<10	270	2833	16	123	25	17	57
165461	1305421	0.021	<1	4.49	30	289	<2	<1	0.51	<4	11	63	6	2.69	0.35	4	0.40	355	7	104	517	22	2.51	<5	<5	<10	60	1695	<2	40	<10	9	126
165462D	1305421	0.017	<1	3.78	27	241	<2	3	0.43	<4	10	56	7	2.59	0.26	3	0.36	319	5	94	499	22	2.52	<5	<5	<10	54	1540	<2	35	<10	8	125
165463	1305422	0.078	2	4.38	59	206	2	6	0.09	4	17	61	7	5.96	0.17	2	0.17	150	8	118	493	22	6.65	<5	<5	<10	52	1612	2	38	13	8	688

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, July 15, 2012

Final Certificate

Treasury Metals Inc
Exchange Tower 130 King St Suite 3680
Toronto, On, CAN
M5X 1B1
Ph#: (416) 599-4133
Fax#: (416) 599-4959
Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 06/11/2012
Date Completed: 06/22/2012
Job #: 201242025
Reference: TL 12258
Sample #: 127

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
165464	1305423	0.007	<1	5.27	16	254	<2	1	2.08	<4	9	45	6	2.04	0.14	13	1.14	627	3	73	540	26	1.07	<5	7	<10	80	1558	<2	34	<10	7	69
165465	1305424	<0.005	<1	5.51	21	280	<2	3	2.15	<4	7	65	4	2.03	0.14	15	1.41	739	7	105	472	24	0.66	<5	<5	<10	95	1470	11	41	<10	6	121
165466	1305425	0.021	<1	4.13	21	262	<2	<1	1.18	<4	8	67	4	1.86	0.12	5	0.66	456	7	98	502	23	1.31	<5	<5	<10	86	1011	<2	30	<10	6	70
165467	1305426	0.015	<1	3.82	30	220	<2	<1	1.16	<4	7	55	12	2.04	0.11	4	0.87	482	5	96	454	24	1.59	<5	<5	<10	87	917	6	31	<10	5	56
165468	1305427	0.017	<1	5.20	28	247	<2	<1	1.34	<4	7	54	10	1.96	0.20	6	0.93	452	4	88	496	81	1.52	<5	<5	<10	88	1058	2	34	<10	5	89
165469	1305428	0.036	<1	5.16	59	228	<2	4	1.19	<4	9	51	13	2.29	0.17	6	0.81	444	4	81	511	50	1.98	<5	<5	<10	79	1105	<2	33	<10	6	59
165470	1305429	1.348	10	4.72	151	291	<2	3	0.36	4	7	90	82	1.95	0.25	3	0.40	214	15	160	478	564	1.51	39	<5	<10	57	1119	<2	38	16	5	1111
165471	1305430	0.257	<1	<0.01	455	>5000	<2	<1	0.82	<4	8	22	32	3.07	<0.01	<1	0.05	<100	9	20	<100	27	0.59	21	6	<10	104	950	3	16	55	7	33
165472	1305431	0.802	1	3.26	101	275	2	5	<0.01	6	7	73	27	2.39	0.18	2	0.22	107	10	128	396	180	2.33	11	<5	<10	40	979	<2	32	21	4	1454
165473D	1305431	0.810	<1	3.21	100	258	<2	<1	<0.01	6	7	50	28	2.28	0.15	2	0.22	<100	5	85	394	176	2.37	12	<5	<10	39	949	2	29	23	4	1420
165474	1305432	3.038	6	3.41	137	304	<2	1	<0.01	<4	6	59	89	1.61	0.13	<1	0.17	<100	7	100	411	504	1.56	46	<5	<10	47	932	8	31	16	4	722
165475	1305433	0.560	2	3.33	170	377	2	2	<0.01	15	7	52	64	2.55	0.12	<1	0.17	<100	5	85	373	376	2.93	30	<5	<10	45	950	5	30	52	4	4516
165476	1305434	0.427	4	3.15	122	404	<2	<1	<0.01	<4	6	30	40	1.40	0.13	<1	0.22	<100	<1	47	391	248	1.41	19	<5	<10	39	1227	2	28	12	5	442
165477	1305435	0.037	<1	4.79	30	346	<2	<1	1.88	<4	7	43	13	1.77	<0.01	9	1.06	664	2	69	496	40	0.82	<5	<5	<10	79	1601	4	33	<10	6	69
165478	1305436	0.046	<1	4.93	39	332	2	2	1.89	<4	7	33	12	1.68	0.04	10	1.08	678	<1	50	500	36	0.77	<5	<5	<10	78	1571	5	32	<10	6	66
165479	1305437	0.245	<1	4.41	76	216	<2	<1	2.02	<4	13	126	36	2.54	0.04	7	1.01	519	6	116	425	26	1.19	<5	<5	<10	82	1887	6	55	<10	10	66
165480	1305438	0.049	<1	5.43	22	246	2	8	1.96	<4	15	102	33	2.91	0.01	12	1.24	546	<1	74	514	27	1.09	<5	5	<10	81	2274	19	62	<10	11	79
165481	1305439	0.491	<1	5.48	26	268	2	<1	1.69	<4	19	135	76	3.64	0.04	11	1.29	559	<1	81	535	48	2.05	<5	<5	<10	123	2193	2	70	13	14	413
165482	1305440	0.006	<1	2.76	4	252	<2	2	1.96	<4	15	49	21	3.18	0.12	6	1.18	614	<1	33	546	9	0.18	<5	<5	<10	201	2341	10	105	15	14	51
165483	1305441	0.268	2	4.25	76	338	<2	<1	0.35	5	11	66	64	2.25	0.11	2	0.34	172	<1	62	467	295	1.91	<5	<5	<10	45	1706	<2	50	22	8	1291

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
Jason Moore, General Manager

The results included on this report relate only to the items tested.
The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, July 15, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/11/2012
 Date Completed: 06/22/2012
 Job #: 201242025
 Reference: TL 12258
 Sample #: 127

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
165484D	1305441	0.278	2	4.47	77	344	<2	3	0.38	6	11	67	65	2.29	0.14	3	0.35	174	<1	65	481	306	1.97	<5	<5	<10	45	1731	<2	50	21	8	1334
165485	1305442	0.209	<1	3.79	68	285	<2	<1	0.16	<4	9	57	17	1.68	<0.01	2	0.32	134	<1	55	409	107	1.67	<5	<5	<10	42	1481	<2	42	12	6	301
165486	1305443	0.155	<1	4.22	51	230	2	2	0.69	<4	20	132	32	3.50	<0.01	6	0.76	384	2	105	518	60	2.61	<5	<5	<10	58	1599	3	67	<10	13	219
165487	1305444	0.100	<1	4.34	<2	228	2	3	1.15	<4	24	128	54	3.76	0.14	7	1.07	536	<1	113	526	44	2.00	<5	<5	<10	73	1726	<2	72	<10	15	88
165488	1305445	0.494	2	5.24	26	260	2	6	1.02	<4	13	102	96	2.97	0.14	7	0.77	385	5	105	572	322	1.84	<5	<5	<10	66	1651	<2	60	12	12	326
165489	1305446	0.529	1	4.63	75	344	<2	5	<0.01	5	7	41	74	1.79	0.07	5	0.27	<100	3	63	449	485	1.70	17	5	<10	39	1658	<2	34	21	6	1224
165490	1305447	0.301	<1	4.14	90	354	<2	<1	0.06	<4	7	37	18	1.54	0.25	4	0.33	136	2	58	456	49	1.45	<5	<5	<10	42	1590	<2	34	13	6	206
165491	1305448	0.212	<1	5.20	65	364	<2	3	1.35	<4	7	39	14	1.74	0.05	9	0.94	767	2	58	481	86	1.22	<5	<5	<10	77	1652	4	33	11	6	309
165492	1305449	0.156	<1	5.05	32	354	<2	<1	2.05	<4	8	31	12	1.62	0.07	9	1.14	1050	<1	44	453	65	0.88	<5	<5	<10	89	1612	3	33	<10	6	138
165493	1305450	4.867	68	2.96	36	367	<2	<1	1.24	21	13	34	50	3.12	0.04	6	0.74	487	<1	29	505	600	0.53	55	<5	236	198	1786	10	87	56	13	1876
165494	1305451	0.104	<1	4.57	16	323	2	<1	1.30	<4	8	58	69	2.11	0.26	8	0.94	665	5	92	492	152	1.14	<5	<5	<10	75	1620	8	35	15	6	384
165495R	1305451	0.117	<1	3.26	18	253	2	9	1.26	<4	8	34	48	1.82	0.14	5	0.90	668	<1	57	463	148	1.05	<5	<5	<10	72	1399	7	29	13	5	289
165496	1305452	1.248	2	2.95	65	308	<2	5	0.13	7	6	52	256	2.37	0.16	3	0.32	198	5	81	396	442	2.13	5	<5	<10	37	1409	<2	30	27	5	1825
165497	1305453	1.297	<1	4.00	74	247	2	1	1.19	<4	13	79	44	2.65	0.01	7	0.97	553	<1	81	503	65	1.84	<5	<5	<10	84	1789	7	52	10	9	115
165498	1305454	0.129	<1	3.63	4	254	<2	<1	1.08	<4	21	128	73	3.49	<0.01	13	1.10	568	<1	93	498	46	0.99	<5	<5	<10	88	2374	<2	72	<10	13	123
165499	1305455	0.452	2	2.08	33	306	<2	<1	0.06	4	5	38	113	1.39	0.07	<1	0.28	127	<1	59	429	378	1.12	<5	<5	<10	42	1348	<2	29	15	5	749
165500	1305456	0.401	<1	2.14	36	316	<2	2	0.06	4	6	26	125	1.38	0.30	<1	0.29	120	<1	41	413	303	1.23	<5	<5	<10	49	1359	2	29	13	5	801
165501	1305457	0.499	<1	1.95	36	292	<2	<1	0.51	5	6	25	56	1.90	0.14	2	0.49	279	<1	41	371	230	1.85	<5	<5	<10	53	1162	<2	23	20	4	1277
165502	1305458	0.019	<1	3.74	3	311	<2	3	2.44	<4	7	27	19	1.78	0.06	9	1.42	630	<1	43	463	31	0.63	<5	<5	<10	105	1402	5	30	<10	5	74

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AlSu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 22, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/11/2012
 Date Completed: 06/22/2012
 Job #: 201242025
 Reference: TL 12258
 Sample #: 127

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
165364	1305332	83	0.002	0.083
165365	1305333	26	<0.001	0.026
165366	1305334	87	0.003	0.087
165367	1305335	26	<0.001	0.026
165368	1305336	27	<0.001	0.027
165369	1305337	68	0.002	0.068
165370	1305338	38	0.001	0.038
165371	1305339	31	<0.001	0.031
165372	1305340	11	<0.001	0.011
165373	1305341	9	<0.001	0.009
165374 Dup	1305341	5	<0.001	0.005
165375	1305342	8	<0.001	0.008
165376	1305343	11	<0.001	0.011
165377	1305344	17	<0.001	0.017
165378	1305345	10	<0.001	0.010
165379	1305346	9	<0.001	0.009
165380	1305347	12	<0.001	0.012
165381	1305348	12	<0.001	0.012
165382	1305349	57	0.002	0.057
165383	1305350	1930	0.056	1.930
165384	1305351	76	0.002	0.076
165385 Dup	1305351	79	0.002	0.079
165386	1305352	201	0.006	0.201
165387	1305353	15	<0.001	0.015
165388	1305354	41	0.001	0.041
165389	1305355	13	<0.001	0.013
165390	1305356	24	<0.001	0.024
165391	1305357	20	<0.001	0.020
165392	1305358	22	<0.001	0.022
165393	1305359	62	0.002	0.062

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.

The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 22, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/11/2012
 Date Completed: 06/22/2012
 Job #: 201242025
 Reference: TL 12258
 Sample #: 127

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
165394	1305360	9	<0.001	0.009
165395	1305361	23	<0.001	0.023
165396 Dup	1305361	27	<0.001	0.027
165397	1305362	26	<0.001	0.026
165398	1305363	27	<0.001	0.027
165399	1305364	21	<0.001	0.021
165400	1305365	18	<0.001	0.018
165401	1305366	11	<0.001	0.011
165402	1305367	259	0.008	0.259
165403	1305368	61	0.002	0.061
165404	1305369	326	0.010	0.326
165405	1305370	221	0.006	0.221
165406	1305371	561	0.016	0.561
165407 Dup	1305371	575	0.017	0.575
165408	1305372	1536	0.045	1.536
165409	1305373	295	0.009	0.295
165410	1305374	140	0.004	0.140
165411	1305375	54	0.002	0.054
165412	1305376	63	0.002	0.063
165413	1305377	90	0.003	0.090
165414	1305378	486	0.014	0.486
165415	1305379	202	0.006	0.202
165416	1305380	5	<0.001	0.005
165417	1305381	455	0.013	0.455
165418 Dup	1305381	469	0.014	0.469
165419	1305382	34	0.001	0.034
165420	1305383	66	0.002	0.066
165421	1305384	995	0.029	0.995
165422	1305385	121	0.004	0.121
165423	1305386	11	<0.001	0.011

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.

The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 22, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/11/2012
 Date Completed: 06/22/2012
 Job #: 201242025
 Reference: TL 12258
 Sample #: 127

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
165424	1305387	17	<0.001	0.017
165425	1305388	9	<0.001	0.009
165426	1305389	9	<0.001	0.009
165427	1305390	5436	0.159	5.436
165428	1305391	13	<0.001	0.013
165429 Rep	1305391	12	<0.001	0.012
165430	1305392	12	<0.001	0.012
165431	1305393	13	<0.001	0.013
165432	1305394	12	<0.001	0.012
165433	1305395	10	<0.001	0.010
165434	1305396	9	<0.001	0.009
165435	1305397	<5	<0.001	<0.005
165436	1305398	7	<0.001	0.007
165437	1305399	7	<0.001	0.007
165438	1305400	<5	<0.001	<0.005
165439	1305401	17	<0.001	0.017
165440 Dup	1305401	13	<0.001	0.013
165441	1305402	<5	<0.001	<0.005
165442	1305403	6	<0.001	0.006
165443	1305404	18	<0.001	0.018
165444	1305405	20	<0.001	0.020
165445	1305406	7	<0.001	0.007
165446	1305407	10	<0.001	0.010
165447	1305408	8	<0.001	0.008
165448	1305409	10	<0.001	0.010
165449	1305410	1952	0.057	1.952
165450	1305411	47	0.001	0.047
165451 Dup	1305411	33	<0.001	0.033
165452	1305412	<5	<0.001	<0.005
165453	1305413	9	<0.001	0.009

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 22, 2012

Certificate of Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/11/2012
 Date Completed: 06/22/2012
 Job #: 201242025
 Reference: TL 12258
 Sample #: 127

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
165454	1305414	13	<0.001	0.013
165455	1305415	361	0.011	0.361
165456	1305416	283	0.008	0.283
165457	1305417	7	<0.001	0.007
165458	1305418	10	<0.001	0.010
165459	1305419	40	0.001	0.040
165460	1305420	<5	<0.001	<0.005
165461	1305421	21	<0.001	0.021
165462 Dup	1305421	17	<0.001	0.017
165463	1305422	78	0.002	0.078
165464	1305423	7	<0.001	0.007
165465	1305424	<5	<0.001	<0.005
165466	1305425	21	<0.001	0.021
165467	1305426	15	<0.001	0.015
165468	1305427	17	<0.001	0.017
165469	1305428	36	0.001	0.036
165470	1305429	1348	0.039	1.348
165471	1305430	257	0.007	0.257
165472	1305431	802	0.023	0.802
165473 Dup	1305431	810	0.024	0.810
165474	1305432	3038	0.089	3.038
165475	1305433	560	0.016	0.560
165476	1305434	427	0.012	0.427
165477	1305435	37	0.001	0.037
165478	1305436	46	0.001	0.046
165479	1305437	245	0.007	0.245
165480	1305438	49	0.001	0.049
165481	1305439	491	0.014	0.491
165482	1305440	6	<0.001	0.006
165483	1305441	268	0.008	0.268

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, June 22, 2012

Certificate of Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 06/11/2012
 Date Completed: 06/22/2012
 Job #: 201242025
 Reference: TL 12258
 Sample #: 127

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
165484 Dup	1305441	278	0.008	0.278
165485	1305442	209	0.006	0.209
165486	1305443	155	0.005	0.155
165487	1305444	100	0.003	0.100
165488	1305445	494	0.014	0.494
165489	1305446	529	0.015	0.529
165490	1305447	301	0.009	0.301
165491	1305448	212	0.006	0.212
165492	1305449	156	0.005	0.156
165493	1305450	4867	0.142	4.867
165494	1305451	104	0.003	0.104
165495 Rep	1305451	117	0.003	0.117
165496	1305452	1248	0.036	1.248
165497	1305453	1297	0.038	1.297
165498	1305454	129	0.004	0.129
165499	1305455	452	0.013	0.452
165500	1305456	401	0.012	0.401
165501	1305457	499	0.015	0.499
165502	1305458	19	<0.001	0.019

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AlSu1

 Certified By: 
 Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.

The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, July 15, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/21/2012
 Date Completed: 07/05/2012
 Job #: 201242284
 Reference: TL12 259
 Sample #: 81

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
176070	1360554	0.110	2	8.89	26	621	2	19	1.10	<4	6	49	25	1.37	0.53	23	0.56	273	8	47	450	215	1.63	<5	33	<10	123	2184	<2	36	12	7	383
176071	1360555	0.140	<1	8.12	10	433	2	28	1.37	<4	5	60	37	1.73	0.75	20	0.70	487	9	67	505	68	1.37	<5	34	<10	139	1717	5	33	11	8	97
176072	1360556	0.023	<1	6.52	7	394	2	19	1.14	<4	5	57	27	1.37	0.54	15	0.58	411	8	62	508	59	1.00	6	22	<10	120	1496	<2	28	<10	7	100
176073	1360557	0.025	1	>10.00	11	663	2	26	2.11	<4	10	141	12	2.11	0.25	31	1.31	536	13	111	729	38	1.24	<5	23	<10	142	2759	13	54	10	10	78
176074	1360558	0.041	<1	8.43	19	421	2	29	1.02	<4	6	52	10	0.95	0.37	19	0.72	447	8	58	340	111	0.90	<5	33	<10	119	1607	<2	29	10	7	119
176075	1360559	0.119	<1	9.62	19	427	2	31	1.36	<4	6	53	6	0.85	0.34	20	0.79	511	10	59	373	110	0.86	6	28	<10	130	1759	3	30	13	7	328
176076	1360560	0.236	2	4.56	433	>5000	2	23	1.18	<4	6	35	30	2.80	0.47	11	0.06	<100	18	17	<100	29	0.75	22	19	<10	125	1226	<2	18	58	11	32
176077	1360561	0.033	<1	9.21	22	546	2	38	1.28	<4	6	62	9	1.06	0.33	17	0.67	534	13	88	359	51	1.16	5	30	<10	111	1542	3	29	10	7	55
176078	1360562	0.065	<1	9.16	25	482	2	27	0.63	<4	8	57	23	1.19	0.30	17	0.50	330	11	69	394	49	1.56	7	32	<10	81	1703	<2	33	11	6	147
176079	1360563	0.310	1	7.97	27	403	2	40	0.14	<4	8	60	34	1.27	0.47	9	0.25	<100	10	80	369	193	1.74	13	29	<10	62	1531	<2	32	10	6	175
176080D	1360563	0.206	2	8.36	34	405	2	28	0.19	<4	8	63	35	1.29	0.64	11	0.24	<100	11	79	370	201	1.68	13	33	<10	64	1590	<2	33	11	6	178
176081	1360564	0.599	4	7.49	35	376	2	16	0.20	<4	5	59	52	1.25	0.42	9	0.20	<100	14	79	272	460	1.68	11	25	<10	52	1252	<2	26	11	6	544
176082	1360565	0.164	<1	9.97	29	758	2	27	0.26	<4	5	53	13	1.28	0.48	20	0.40	117	9	57	467	98	1.67	<5	27	<10	66	2119	<2	46	11	7	172
176083	1360566	0.073	<1	5.22	19	288	2	22	<0.01	<4	5	57	7	0.81	0.25	2	0.22	<100	6	80	346	89	0.81	<5	17	<10	49	1328	<2	26	<10	5	120
176084	1360567	0.144	6	6.07	18	292	2	10	0.05	13	3	54	56	0.95	0.26	4	0.18	<100	9	75	362	799	1.45	8	23	<10	54	1246	<2	25	51	5	4564
176085	1360568	0.539	5	8.97	42	364	2	28	0.25	<4	3	57	94	1.05	0.19	10	0.20	<100	11	70	379	107	1.34	21	26	<10	63	1454	<2	27	15	7	841
176086	1360569	0.120	1	9.41	20	375	2	36	0.65	<4	3	58	13	0.95	0.29	16	0.42	319	12	65	334	62	1.11	6	31	<10	77	1429	<2	29	10	7	220
176087	1360570	0.012	<1	8.75	9	446	<2	31	2.73	<4	16	68	22	3.50	0.60	17	1.32	708	3	35	587	13	0.11	<5	16	<10	293	3423	<2	121	28	19	59
176088	1360571	0.270	2	9.40	26	345	2	32	0.33	<4	3	69	17	1.12	0.25	15	0.24	<100	16	90	340	74	1.27	5	28	<10	57	1452	<2	30	11	8	317
176089	1360572	0.227	5	>10.00	19	427	2	27	0.46	<4	4	67	13	1.13	0.30	21	0.29	103	19	82	374	106	1.29	5	34	<10	82	1723	<2	35	<10	8	109

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, July 15, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/21/2012
 Date Completed: 07/05/2012
 Job #: 201242284
 Reference: TL12 259
 Sample #: 81

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
176090	1360573	0.265	27	9.71	19	388	2	34	0.87	<4	4	68	14	1.05	0.36	23	0.48	371	14	83	352	104	1.07	10	28	<10	137	1577	<2	34	11	7	372
176091D	1360573	0.251	25	8.18	18	372	2	33	0.79	<4	4	57	14	0.97	0.44	21	0.45	366	13	69	342	106	1.07	5	20	<10	133	1524	2	33	13	6	371
176092	1360574	0.027	2	8.98	23	359	2	30	1.27	<4	4	60	9	1.40	0.30	26	0.70	635	13	87	364	32	1.49	8	28	<10	141	1767	<2	33	12	7	38
176093	1360575	0.021	<1	8.27	17	318	2	29	1.91	<4	4	57	5	1.57	0.35	24	1.01	910	10	79	421	43	1.77	<5	34	<10	175	1458	<2	28	<10	7	55
176094	1360576	0.020	<1	8.86	20	298	2	36	1.87	<4	3	75	6	1.47	0.33	25	0.94	862	15	98	338	34	1.42	<5	31	<10	143	1449	4	29	11	8	43
176095	1360577	0.018	<1	7.70	12	370	2	34	2.43	<4	17	45	16	4.26	0.13	18	0.77	329	6	76	362	31	7.49	5	24	<10	226	1664	<2	36	<10	8	274
176096	1360578	0.015	<1	8.00	9	428	2	30	2.20	<4	7	43	6	2.12	0.30	24	1.08	245	5	55	443	32	3.06	5	29	<10	309	1495	<2	38	11	7	78
176097	1360579	0.014	<1	9.08	33	414	2	24	2.75	<4	6	38	40	2.31	0.13	22	0.93	265	5	54	469	44	3.92	<5	24	<10	375	1473	<2	43	10	8	263
176098	1360580	1.840	<1	8.76	11	494	2	40	2.80	<4	18	71	38	4.16	0.31	19	1.39	781	5	37	646	19	0.26	6	28	<10	303	3595	4	135	31	19	87
176099	1360581	0.006	<1	8.74	10	505	2	28	2.58	<4	7	58	12	1.74	0.11	25	0.64	245	11	77	464	22	2.56	5	32	<10	345	1713	<2	48	10	7	41
176100	1360582	0.006	<1	9.16	22	573	2	39	1.69	<4	13	68	5	2.05	0.15	29	0.39	146	16	107	446	23	3.23	<5	37	<10	300	1829	<2	43	15	6	880
176101	1360583	0.010	<1	8.78	18	413	2	30	1.65	<4	8	61	3	1.71	0.10	26	0.40	125	11	71	384	21	2.42	5	29	<10	271	1717	<2	36	<10	7	41
176102D	1360583	0.008	<1	8.65	10	404	2	21	1.68	<4	8	56	3	1.77	0.21	25	0.45	128	8	75	398	23	2.48	<5	26	<10	282	1708	<2	37	<10	7	32
176103	1360584	0.007	<1	8.89	10	356	2	26	1.85	<4	7	72	6	1.47	0.27	22	0.42	163	13	95	365	27	1.67	<5	22	<10	294	1584	<2	36	<10	7	24
176104	1360585	0.011	<1	7.99	79	453	2	42	1.79	<4	8	71	17	2.14	0.25	24	0.62	306	8	92	422	29	2.86	5	28	<10	280	1765	<2	43	11	8	33
176105	1360586	0.010	<1	6.19	24	474	2	24	0.82	<4	10	67	30	2.26	0.19	15	0.35	207	7	89	410	29	3.15	<5	22	<10	244	1901	<2	43	10	8	56
176106	1360587	0.010	<1	8.52	13	458	2	35	1.52	<4	8	79	12	2.03	0.24	25	0.66	306	13	97	416	27	2.23	<5	31	<10	248	1732	<2	41	11	7	49
176107	1360588	0.009	<1	8.29	23	582	2	30	1.55	<4	10	94	14	2.43	0.27	22	0.63	320	11	94	445	25	2.86	<5	21	<10	318	1929	<2	53	<10	8	53
176108	1360589	0.008	1	7.02	26	630	3	30	2.59	<4	15	106	30	2.96	0.20	24	0.85	617	9	85	601	29	2.38	<5	23	<10	318	2465	<2	69	11	8	68
176109	1360590	<0.005	<1	4.18	4	321	<2	21	2.34	<4	16	58	23	3.57	0.09	9	1.34	705	<1	32	597	16	0.20	<5	17	<10	240	2923	3	116	23	16	57

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, July 15, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/21/2012
 Date Completed: 07/05/2012
 Job #: 201242284
 Reference: TL12 259
 Sample #: 81

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
176110	1360591	0.023	2	7.85	54	505	2	25	1.46	<4	12	81	22	2.68	0.12	16	0.75	718	6	78	554	41	3.55	<5	14	<10	185	1914	<2	59	<10	10	83
176111	1360592	0.009	3	8.45	59	520	2	29	1.29	<4	9	63	15	1.96	0.17	20	0.49	915	10	69	555	48	2.39	6	29	<10	162	1689	<2	48	<10	7	108
176112	1360593	0.010	5	8.26	51	471	2	18	1.20	<4	8	67	25	1.74	0.04	19	0.47	986	12	76	517	70	1.90	<5	28	<10	148	1451	<2	46	<10	6	193
176113D	1360593	0.013	6	8.76	52	475	2	33	1.22	<4	8	66	26	1.81	0.06	18	0.51	1023	12	82	531	74	1.98	6	31	<10	154	1465	<2	48	10	7	204
176114	1360594	0.088	60	7.94	62	371	2	23	0.24	<4	7	69	27	1.58	0.19	10	0.16	<100	11	87	442	145	2.11	19	18	<10	87	1375	4	40	10	8	420
176115	1360595	0.022	4	8.13	42	419	2	25	0.68	<4	8	61	15	1.88	0.17	14	0.32	574	9	82	489	54	2.34	<5	31	<10	118	1653	<2	43	<10	7	101
176116	1360596	0.031	4	8.18	43	436	2	28	0.65	<4	8	42	16	1.79	0.17	15	0.27	429	5	36	479	45	2.57	<5	25	<10	111	1672	<2	41	<10	7	92
176117	1360597	0.017	<1	5.21	21	362	2	11	1.60	<4	9	34	16	1.93	0.15	14	0.73	816	<1	38	548	31	1.50	<5	14	<10	156	1800	2	38	<10	7	72
176118	1360598	0.074	1	6.97	26	323	<2	21	0.74	<4	8	41	20	1.89	0.07	10	0.42	350	5	82	425	27	2.13	<5	20	<10	64	1814	<2	39	12	7	165
176119	1360599	0.006	<1	6.57	11	251	2	23	1.90	<4	6	41	9	1.46	0.16	14	0.91	612	5	41	383	27	0.86	<5	25	<10	75	1716	<2	34	<10	6	51
176120	1360600	4.943	69	5.43	44	466	<2	20	1.54	19	14	41	51	3.28	0.43	10	0.80	524	3	28	526	588	0.77	71	17	245	235	2170	<2	93	63	15	1853
176121	1360601	0.007	<1	7.77	15	323	<2	36	2.53	<4	8	35	24	1.90	0.11	17	1.34	597	2	45	498	38	1.31	<5	30	<10	84	1961	7	37	<10	8	107
176122	1360602	0.014	2	7.52	9	329	2	29	2.31	<4	5	51	17	1.55	0.19	13	1.17	827	8	46	423	33	0.75	<5	15	<10	77	1329	8	33	<10	8	88
176123	1360603	0.080	1	9.00	31	417	2	32	0.63	<4	7	44	101	1.69	0.12	12	0.31	174	7	42	474	56	2.35	<5	17	<10	74	1734	<2	42	11	7	157
176124D	1360603	0.058	<1	8.51	28	401	2	22	0.55	<4	7	40	17	1.74	0.27	11	0.30	158	6	34	469	55	2.50	<5	25	<10	73	1688	2	42	13	7	152
176125	1360604	0.433	5	8.00	49	358	2	28	0.34	<4	7	42	22	1.80	0.35	9	0.19	<100	5	43	448	91	3.05	<5	29	<10	73	1322	3	39	15	6	540
176126	1360605	0.254	1	7.45	43	347	2	34	0.19	<4	6	39	12	1.70	0.49	6	0.13	<100	4	47	451	109	2.85	10	18	<10	76	1259	<2	40	12	6	375
176127	1360606	0.175	<1	7.14	65	348	3	31	0.47	<4	7	44	23	1.96	0.19	9	0.37	134	6	50	462	173	3.08	9	25	<10	83	1144	<2	38	12	6	482
176128	1360607	2.316	4	6.26	84	346	<2	30	0.30	<4	6	40	35	1.63	0.25	7	0.29	<100	5	50	415	339	2.58	25	25	<10	67	1113	<2	34	13	6	176
176129	1360608	0.514	<1	7.41	63	392	3	23	0.56	<4	7	42	35	1.61	0.13	10	0.47	211	6	55	434	125	2.24	10	26	<10	71	1287	<2	38	16	6	516

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By:  Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, July 15, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/21/2012
 Date Completed: 07/05/2012
 Job #: 201242284
 Reference: TL12 259
 Sample #: 81

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
176130	1360609	0.734	3	6.76	131	352	2	18	0.26	6	7	39	68	2.04	0.21	7	0.21	<100	5	39	393	214	3.58	21	21	<10	53	1252	<2	34	34	6	2381
176131	1360610	0.005	<1	6.47	9	402	2	21	2.44	<4	15	61	22	3.27	0.37	13	1.14	657	1	33	555	19	0.25	<5	8	<10	269	3092	<2	113	28	14	104
176132	1360611	0.240	<1	5.40	73	393	2	20	0.65	<4	8	46	15	2.22	0.31	7	0.56	324	4	52	427	99	3.30	5	22	<10	57	1529	<2	36	12	6	111
176133	1360612	0.031	<1	7.24	33	449	2	26	1.93	<4	7	49	6	1.61	0.16	16	0.98	624	8	56	441	36	0.97	<5	22	<10	74	1942	3	40	13	6	65
176134	1360613	0.250	2	7.19	33	378	2	26	1.65	<4	20	168	45	3.54	0.21	17	0.98	489	7	90	475	316	2.39	<5	21	<10	102	2912	<2	87	18	12	529
176135R	1360613	0.171	2	8.08	26	406	2	30	1.74	<4	21	177	48	3.71	0.19	20	1.01	504	8	83	501	326	2.53	<5	16	<10	107	3068	2	92	12	13	549
176136	1360614	0.097	<1	7.58	8	336	3	18	2.06	<4	23	162	55	3.91	0.06	20	1.21	733	4	81	476	61	2.19	<5	22	<10	114	3165	15	99	12	12	125
176137	1360615	0.154	<1	8.60	30	443	2	26	1.40	<4	23	170	59	3.68	0.24	18	0.82	473	8	102	467	89	3.53	<5	21	<10	81	2981	<2	102	15	14	86
176138	1360616	0.128	<1	7.55	31	397	3	12	1.26	<4	23	162	61	3.64	0.20	14	0.90	476	4	98	454	88	3.52	<5	21	<10	78	2776	<2	98	12	16	77
176139	1360617	1.260	2	7.91	103	424	2	19	0.76	4	8	51	45	1.74	0.48	10	0.49	324	6	48	408	402	2.42	14	16	<10	62	1974	<2	40	25	7	1231
176140	1360618	0.849	1	6.92	60	463	2	20	0.28	<4	7	43	39	1.61	0.15	11	0.31	146	5	50	412	149	2.14	<5	20	<10	45	1936	<2	37	17	6	409
176141	1360619	0.260	<1	7.32	59	427	2	19	1.42	<4	7	38	11	1.66	0.49	14	0.93	705	3	36	451	66	1.91	<5	31	<10	85	1966	<2	39	13	7	103
176142	1360620	0.261	<1	2.70	391	>5000	<2	25	1.00	<4	7	28	27	2.67	0.27	6	0.07	<100	13	13	<100	27	0.83	16	10	<10	111	1066	<2	17	50	9	24
176143	1360621	0.523	<1	6.14	77	668	2	23	0.68	<4	7	43	57	1.56	0.37	11	0.45	287	5	43	367	63	1.95	<5	21	<10	63	1704	<2	35	15	6	274
176144	1360622	0.625	1	4.83	113	297	2	22	0.20	<4	17	122	88	2.97	0.41	6	0.39	150	3	75	417	311	4.33	5	<5	<10	47	1875	<2	65	12	10	317
176145	1360623	0.177	<1	6.65	24	274	2	28	1.27	<4	22	148	46	3.97	0.10	17	1.17	529	1	85	476	51	2.29	<5	21	<10	86	2731	<2	93	11	15	136
176146D	1360623	0.093	<1	6.33	18	304	2	24	1.28	<4	23	158	46	3.99	0.05	19	1.09	543	3	85	466	49	2.20	<5	16	<10	87	2939	<2	101	<10	11	135
176147	1360624	0.143	<1	6.70	56	456	2	23	1.26	<4	14	96	40	2.51	<0.01	13	0.71	351	5	68	433	82	2.90	<5	16	<10	95	2211	<2	59	10	10	177
176148	1360625	0.100	<1	7.65	26	526	2	24	1.15	<4	7	54	24	1.65	0.11	16	0.65	376	8	55	417	185	1.74	5	24	<10	78	1941	<2	38	20	7	730
176149	1360626	0.058	<1	6.53	4	389	3	31	3.29	<4	6	36	30	1.92	0.06	11	1.99	768	6	33	405	55	1.11	<5	18	<10	94	1695	14	37	76	7	303

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Sunday, July 15, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/21/2012
 Date Completed: 07/05/2012
 Job #: 201242284
 Reference: TL12 259
 Sample #: 81

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
176150	1360627	0.036	<1	6.89	9	477	2	32	1.80	<4	8	40	76	2.68	0.13	14	1.00	338	4	33	396	126	2.44	<5	21	<10	93	1576	2	33	15	7	406
176151	1360628	0.009	<1	6.03	7	434	3	19	3.68	<4	6	53	16	1.97	0.11	13	1.96	793	3	46	436	35	0.98	5	18	<10	115	1700	17	37	11	7	90
176152	1360629	0.644	<1	7.21	18	443	2	22	1.87	4	7	53	31	1.69	0.17	20	0.91	482	8	58	441	67	1.13	<5	23	<10	99	2093	<2	40	22	6	1441
176153	1360630	<0.005	<1	6.64	8	402	2	12	2.51	<4	15	59	22	3.33	0.52	12	1.25	676	1	30	557	15	0.21	5	16	<10	277	3120	<2	114	27	17	81
176154	1360631	1.293	6	6.96	20	503	2	31	1.50	12	7	55	380	2.23	0.18	19	0.72	365	8	66	428	686	2.79	6	26	<10	102	2040	<2	41	52	6	3919
176155	1360632	0.068	<1	6.64	14	506	2	22	1.55	<4	7	56	52	1.69	0.16	20	0.96	426	7	58	448	83	0.98	<5	31	<10	91	2131	<2	42	16	5	653
176156	1360633	0.171	<1	6.10	22	356	2	25	1.07	5	7	49	66	2.29	0.09	19	1.93	405	7	67	467	74	1.85	<5	24	<10	80	1858	7	38	21	6	1556
176157D	1360633	0.156	<1	7.25	26	410	2	31	1.15	6	8	52	67	2.32	1.32	22	1.94	408	10	69	481	74	1.91	5	17	<10	83	2018	4	42	22	6	1586
176158	1360634	0.060	<1	6.42	27	447	2	26	1.62	<4	7	60	9	1.84	0.02	15	1.32	469	9	80	440	27	1.67	<5	20	<10	82	1677	5	38	11	6	272

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Thursday, July 5, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/21/2012
 Date Completed: 07/05/2012
 Job #: 201242284
 Reference: TL12 259
 Sample #: 81

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
176070	1360554	110	0.003	0.110
176071	1360555	140	0.004	0.140
176072	1360556	23	<0.001	0.023
176073	1360557	25	<0.001	0.025
176074	1360558	41	0.001	0.041
176075	1360559	119	0.003	0.119
176076	1360560	236	0.007	0.236
176077	1360561	33	<0.001	0.033
176078	1360562	65	0.002	0.065
176079	1360563	310	0.009	0.310
176080 Dup	1360563	206	0.006	0.206
176081	1360564	599	0.017	0.599
176082	1360565	164	0.005	0.164
176083	1360566	73	0.002	0.073
176084	1360567	144	0.004	0.144
176085	1360568	539	0.016	0.539
176086	1360569	120	0.003	0.120
176087	1360570	12	<0.001	0.012
176088	1360571	270	0.008	0.270
176089	1360572	227	0.007	0.227
176090	1360573	265	0.008	0.265
176091 Dup	1360573	251	0.007	0.251
176092	1360574	27	<0.001	0.027
176093	1360575	21	<0.001	0.021
176094	1360576	20	<0.001	0.020
176095	1360577	18	<0.001	0.018
176096	1360578	15	<0.001	0.015
176097	1360579	14	<0.001	0.014
176098	1360580	1840	0.054	1.840
176099	1360581	6	<0.001	0.006

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Thursday, July 5, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/21/2012
 Date Completed: 07/05/2012
 Job #: 201242284
 Reference: TL12 259
 Sample #: 81

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
176100	1360582	6	<0.001	0.006
176101	1360583	10	<0.001	0.010
176102 Dup	1360583	8	<0.001	0.008
176103	1360584	7	<0.001	0.007
176104	1360585	11	<0.001	0.011
176105	1360586	10	<0.001	0.010
176106	1360587	10	<0.001	0.010
176107	1360588	9	<0.001	0.009
176108	1360589	8	<0.001	0.008
176109	1360590	<5	<0.001	<0.005
176110	1360591	23	<0.001	0.023
176111	1360592	9	<0.001	0.009
176112	1360593	10	<0.001	0.010
176113 Dup	1360593	13	<0.001	0.013
176114	1360594	88	0.003	0.088
176115	1360595	22	<0.001	0.022
176116	1360596	31	<0.001	0.031
176117	1360597	17	<0.001	0.017
176118	1360598	74	0.002	0.074
176119	1360599	6	<0.001	0.006
176120	1360600	4943	0.144	4.943
176121	1360601	7	<0.001	0.007
176122	1360602	14	<0.001	0.014
176123	1360603	80	0.002	0.080
176124 Dup	1360603	58	0.002	0.058
176125	1360604	433	0.013	0.433
176126	1360605	254	0.007	0.254
176127	1360606	175	0.005	0.175
176128	1360607	2316	0.068	2.316
176129	1360608	514	0.015	0.514

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Thursday, July 5, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/21/2012
 Date Completed: 07/05/2012
 Job #: 201242284
 Reference: TL12 259
 Sample #: 81

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
176130	1360609	734	0.021	0.734
176131	1360610	5	<0.001	0.005
176132	1360611	240	0.007	0.240
176133	1360612	31	<0.001	0.031
176134	1360613	250	0.007	0.250
176135 Rep	1360613	171	0.005	0.171
176136	1360614	97	0.003	0.097
176137	1360615	154	0.004	0.154
176138	1360616	128	0.004	0.128
176139	1360617	1260	0.037	1.260
176140	1360618	849	0.025	0.849
176141	1360619	260	0.008	0.260
176142	1360620	261	0.008	0.261
176143	1360621	523	0.015	0.523
176144	1360622	625	0.018	0.625
176145	1360623	177	0.005	0.177
176146 Dup	1360623	93	0.003	0.093
176147	1360624	143	0.004	0.143
176148	1360625	100	0.003	0.100
176149	1360626	58	0.002	0.058
176150	1360627	36	0.001	0.036
176151	1360628	9	<0.001	0.009
176152	1360629	644	0.019	0.644
176153	1360630	<5	<0.001	<0.005
176154	1360631	1293	0.038	1.293
176155	1360632	68	0.002	0.068
176156	1360633	171	0.005	0.171
176157 Dup	1360633	156	0.005	0.156
176158	1360634	60	0.002	0.060

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Thursday, August 9, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/05/2012
 Date Completed: 07/20/2012
 Job #: 201242541
 Reference: TL 12 260
 Sample #: 125

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
189818	1360635	0.019	3	8.70	24	632	2	<1	2.38	5	12	45	18	3.33	<0.01	25	1.16	692	3	83	746	650	2.04	<5	<5	<10	284	2715	<2	67	15	9	1371
189819	1360636	0.016	3	>10.00	23	628	2	<1	2.29	5	12	38	14	2.92	<0.01	23	1.05	595	3	70	731	542	2.17	<5	9	<10	303	2626	2	60	13	10	1149
189820	1360637	0.012	2	9.12	14	646	2	<1	2.33	<4	12	36	8	2.85	<0.01	19	0.96	549	1	59	751	28	1.74	5	7	<10	321	3063	3	64	<10	9	92
189821	1360638	0.045	2	9.67	25	634	<2	2	1.50	<4	9	33	19	2.60	<0.01	17	0.69	440	<1	49	742	18	2.41	<5	<5	<10	347	2620	3	59	<10	9	74
189822	1360639	0.114	2	9.16	37	652	2	3	1.55	<4	10	29	12	3.09	<0.01	22	0.86	628	<1	39	643	15	2.64	<5	9	<10	244	2678	<2	52	<10	9	67
189823	1360640	1.760	2	7.91	16	483	2	<1	2.53	<4	15	52	34	3.89	<0.01	16	1.47	732	<1	32	668	10	1.21	<5	10	<10	305	3171	2	124	23	16	53
189824	1360641	0.074	2	8.13	25	605	2	<1	1.57	<4	6	33	16	2.44	<0.01	19	1.00	568	<1	47	634	29	2.30	<5	9	<10	226	2562	3	55	<10	8	58
189825	1360642	0.033	2	8.03	22	588	2	4	1.24	<4	6	27	18	1.81	<0.01	17	0.75	433	<1	46	644	52	1.58	<5	8	<10	195	2537	<2	48	<10	7	86
189826	1360643	0.024	2	6.48	21	521	2	5	1.17	<4	8	39	15	2.42	<0.01	13	0.88	573	1	67	647	22	1.74	<5	6	<10	167	2277	<2	48	<10	8	65
189827	1360644	<0.005	1	7.79	15	479	<2	<1	0.55	<4	6	30	4	0.88	<0.01	13	0.58	189	<1	46	368	26	1.07	<5	13	<10	167	1692	7	37	<10	7	22
189828D	1360644	<0.005	1	5.98	13	414	<2	<1	0.36	<4	5	25	2	0.73	<0.01	9	0.49	154	<1	41	318	24	0.87	<5	10	<10	147	1475	<2	32	<10	6	13
189829	1360645	0.029	2	7.84	15	410	<2	<1	0.64	<4	4	41	11	0.70	<0.01	12	0.50	151	2	61	414	31	1.07	<5	5	<10	210	1532	7	30	<10	6	22
189830	1360646	<0.005	2	7.93	18	466	<2	<1	1.03	<4	6	29	8	0.68	<0.01	13	0.48	155	<1	46	426	22	1.19	<5	9	<10	226	1524	<2	31	<10	6	26
189831	1360647	0.011	2	8.25	15	507	<2	<1	1.31	<4	4	41	8	0.70	0.05	12	0.47	167	3	64	441	26	0.95	<5	<5	<10	261	1494	<2	32	<10	6	<1
189832	1360648	0.013	3	8.22	19	470	<2	<1	1.17	<4	3	28	14	0.67	0.44	14	0.47	164	<1	42	446	13	1.19	<5	12	<10	221	1552	<2	33	<10	7	2
189833	1360649	0.010	2	6.80	13	478	<2	<1	1.33	<4	4	28	9	0.69	0.69	10	0.49	171	<1	40	454	20	0.94	<5	6	<10	242	1487	<2	31	<10	6	6
189834	1360650	0.012	2	6.96	14	440	<2	<1	2.51	<4	14	50	24	3.46	<0.01	10	1.46	679	<1	28	648	4	0.91	<5	<5	<10	307	3010	<2	118	20	18	45
189835	1360651	0.018	2	4.93	10	446	<2	<1	1.22	<4	5	27	12	0.83	0.03	6	0.54	193	<1	43	380	18	0.74	<5	6	<10	217	1364	<2	32	<10	6	8
189836	1360652	0.012	2	6.90	12	623	<2	<1	1.80	<4	8	22	16	1.19	<0.01	14	0.83	356	<1	36	557	27	0.99	<5	5	<10	257	1897	<2	38	<10	7	30
189837	1360653	0.024	2	6.09	10	457	3	<1	1.74	<4	7	21	28	1.68	<0.01	10	0.74	428	<1	36	444	54	1.26	<5	9	<10	230	1486	<2	34	<10	9	91

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, August 9, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/05/2012
 Date Completed: 07/20/2012
 Job #: 201242541
 Reference: TL 12 260
 Sample #: 125

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
189838	1360654	0.013	1	6.57	11	455	<2	<1	2.04	<4	6	18	14	1.75	<0.01	12	0.84	490	<1	31	472	20	1.19	<5	6	<10	224	1692	4	35	<10	7	63
189839D	1360654	0.014	1	5.16	12	423	<2	<1	1.79	<4	6	19	13	1.68	<0.01	8	0.79	471	<1	30	456	17	1.05	<5	7	<10	198	1598	2	33	<10	7	59
189840	1360655	0.024	1	5.17	12	419	<2	<1	1.35	<4	6	18	30	1.64	<0.01	8	0.69	463	<1	29	443	41	1.26	<5	<5	<10	181	1618	2	32	<10	7	97
189841	1360656	0.023	2	6.36	15	468	<2	<1	1.67	<4	7	19	31	1.67	<0.01	9	0.72	483	<1	31	453	52	1.24	<5	5	<10	217	1749	<2	35	<10	7	153
189842	1360657	0.019	2	6.70	22	481	<2	<1	1.78	<4	7	25	32	1.81	<0.01	9	0.78	668	<1	36	473	73	1.28	<5	5	<10	238	1834	3	36	<10	7	102
189843	1360658	0.047	2	6.82	35	527	<2	<1	1.33	<4	7	22	29	2.00	<0.01	7	0.72	604	<1	34	502	186	1.79	<5	<5	<10	200	1843	<2	38	<10	8	406
189844	1360659	0.120	2	6.92	35	518	2	<1	0.60	<4	9	25	18	2.09	<0.01	6	0.57	428	<1	42	500	39	1.93	<5	6	<10	135	1729	<2	36	<10	8	39
189845	1360660	4.595	66	2.77	47	437	<2	<1	1.13	21	13	29	61	3.12	<0.01	<1	0.86	480	<1	23	543	552	0.91	59	10	221	223	1789	3	87	46	13	1778
189846	1360661	0.041	3	7.48	25	604	2	<1	0.68	<4	10	30	20	2.13	<0.01	6	0.67	435	<1	50	616	44	1.51	<5	5	10	130	2039	6	43	<10	9	111
189847	1360662	0.046	2	7.13	43	598	2	<1	1.49	<4	7	22	16	1.93	<0.01	8	0.97	556	<1	33	538	30	1.79	<5	6	<10	127	2058	10	39	<10	7	82
189848	1360663	0.042	2	7.93	33	617	2	3	1.94	<4	9	26	26	2.16	<0.01	10	1.03	751	<1	41	552	33	1.61	<5	6	<10	147	2158	4	39	<10	8	99
189849	1360664	0.029	2	6.11	28	550	<2	<1	0.79	<4	8	18	13	1.80	<0.01	5	0.58	361	<1	31	495	23	1.82	<5	7	<10	125	1953	<2	37	<10	9	194
189850D	1360664	0.039	2	6.54	37	563	<2	<1	0.83	<4	9	20	12	1.90	<0.01	6	0.60	374	<1	36	521	21	1.96	<5	<5	<10	128	2000	2	37	<10	10	84
189851	1360665	0.014	2	5.79	13	456	<2	<1	1.39	<4	6	25	10	1.60	<0.01	7	0.74	478	<1	40	473	8	1.01	<5	6	<10	123	1804	7	33	<10	7	34
189852	1360666	0.027	1	4.76	32	409	<2	<1	0.78	<4	5	21	11	1.38	<0.01	4	0.50	342	<1	32	464	16	1.36	<5	<5	<10	103	1812	<2	35	<10	6	66
189853	1360667	0.024	1	5.76	33	460	<2	<1	0.90	<4	9	27	12	1.17	<0.01	8	0.56	319	<1	33	468	20	1.44	<5	<5	<10	123	1834	5	38	<10	7	36
189854	1360668	0.029	1	3.93	31	427	<2	<1	0.81	<4	4	20	6	1.10	<0.01	3	0.51	218	<1	34	367	23	1.26	<5	8	<10	119	1266	<2	26	<10	5	37
189855	1360669	0.025	1	5.81	27	474	<2	<1	1.80	<4	5	30	19	1.52	<0.01	6	0.75	371	<1	49	424	15	1.63	<5	9	<10	146	1332	2	29	<10	6	69
189856	1360670	0.009	1	4.14	11	388	<2	8	2.21	<4	14	46	24	3.41	<0.01	4	1.38	657	<1	28	610	5	0.63	<5	6	<10	271	2698	6	113	18	16	46
189857	1360671	0.048	3	5.61	32	390	<2	5	1.74	<4	6	32	66	1.74	<0.01	9	0.98	511	<1	50	464	78	1.59	<5	6	<10	152	1538	<2	34	<10	6	428

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, August 9, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/05/2012
 Date Completed: 07/20/2012
 Job #: 201242541
 Reference: TL 12 260
 Sample #: 125

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
189858	1360672	0.044	2	4.83	33	382	<2	<1	1.46	<4	6	21	16	1.52	<0.01	5	0.82	415	<1	32	455	15	1.47	<5	<5	<10	133	1461	2	31	<10	6	68
189859	1360673	0.027	2	6.46	28	482	<2	<1	1.72	<4	4	30	12	1.53	<0.01	10	0.99	426	<1	46	414	17	1.52	<5	<5	<10	135	1449	6	28	<10	6	29
189860	1360674	0.129	2	5.71	46	651	2	<1	0.80	<4	6	23	18	1.60	<0.01	6	0.87	366	<1	33	529	98	2.02	<5	5	<10	113	1794	3	34	<10	6	155
189861D	1360674	0.121	3	6.06	48	686	<2	<1	0.83	<4	7	27	18	1.66	<0.01	7	0.89	381	<1	39	546	101	2.07	<5	<5	<10	116	1871	<2	35	<10	6	162
189862	1360675	0.315	4	5.89	44	665	<2	4	0.31	<4	6	31	33	1.69	<0.01	5	0.59	239	<1	48	617	232	2.00	<5	7	<10	92	1970	<2	36	<10	6	477
189863	1360676	0.257	4	5.11	40	606	<2	<1	0.30	<4	5	22	33	1.58	<0.01	4	0.57	240	<1	37	583	301	1.92	<5	12	<10	92	1854	3	33	<10	6	431
189864	1360677	0.043	2	5.43	19	624	<2	<1	1.62	<4	5	19	11	1.82	<0.01	8	0.98	557	<1	34	544	28	1.40	<5	5	<10	144	1728	<2	33	<10	6	59
189865	1360678	0.061	3	5.04	13	506	<2	<1	1.44	<4	10	11	180	2.03	<0.01	6	0.77	438	<1	20	636	15	1.38	<5	<5	<10	146	1709	9	33	<10	7	30
189866	1360679	0.013	2	4.02	12	506	<2	<1	1.49	<4	4	20	40	1.69	<0.01	5	0.84	401	<1	31	628	12	0.94	<5	9	<10	135	1690	3	32	<10	6	32
189867	1360680	0.235	2	<0.01	427	>5000	<2	<1	0.65	<4	5	13	31	2.85	<0.01	<1	0.21	<100	7	12	101	19	0.97	18	7	<10	102	609	8	15	41	7	13
189868	1360681	0.010	2	4.44	26	823	<2	<1	0.97	<4	3	28	16	1.38	<0.01	8	0.69	403	<1	47	478	22	1.13	<5	9	<10	136	1539	6	29	<10	5	22
189869	1360682	0.096	3	4.51	28	491	<2	<1	1.26	<4	9	64	26	2.25	<0.01	10	1.21	799	<1	64	629	66	1.76	<5	9	<10	137	2026	2	40	<10	7	130
189870	1360683	0.076	3	3.04	24	353	<2	<1	0.20	<4	3	31	16	0.83	<0.01	4	0.51	362	<1	53	335	81	0.89	<5	6	<10	83	1300	<2	26	<10	4	302
189871	1360684	0.042	3	7.95	28	466	<2	3	0.93	<4	6	30	18	0.88	0.05	15	0.74	404	<1	44	448	49	1.20	<5	<5	<10	137	1697	3	33	<10	6	56
189872D	1360684	0.036	3	6.12	22	426	<2	3	0.77	<4	5	26	16	0.77	<0.01	10	0.65	358	<1	40	392	34	1.04	<5	9	<10	124	1535	3	29	<10	5	34
189873	1360685	0.017	2	6.40	20	391	<2	2	1.37	<4	5	27	6	0.74	<0.01	8	0.67	307	<1	45	392	8	0.90	<5	5	<10	143	1379	<2	30	<10	5	1
189874	1360686	0.017	2	4.76	22	365	<2	<1	0.83	<4	4	28	7	0.98	<0.01	7	0.59	258	<1	42	393	10	1.09	<5	6	<10	104	1356	2	27	<10	5	2
189875	1360687	0.014	1	<0.01	7	<1	<2	<1	<0.01	<4	<1	<1	<1	0.06	<0.01	<1	0.20	<100	<1	2	<100	3	0.79	<5	5	<10	30	162	<2	2	<10	3	<1
189876	1360688	0.018	2	4.64	13	313	2	<1	0.90	<4	3	30	16	1.28	<0.01	10	0.84	514	<1	48	383	79	1.00	<5	5	<10	98	1480	4	27	<10	5	165
189877	1360689	0.059	3	4.40	24	294	<2	<1	0.61	<4	2	26	7	1.02	<0.01	7	0.77	453	<1	41	346	95	1.20	<5	7	<10	84	1384	9	25	<10	5	246

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, August 9, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/05/2012
 Date Completed: 07/20/2012
 Job #: 201242541
 Reference: TL 12 260
 Sample #: 125

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
189878	1360690	<0.005	1	4.36	12	372	<2	6	2.16	<4	13	46	22	3.27	<0.01	4	1.35	646	<1	28	600	9	0.67	<5	8	<10	263	2681	<2	110	17	15	45
189879	1360691	0.014	1	4.25	17	256	<2	<1	1.12	<4	2	25	4	1.21	<0.01	7	0.98	636	<1	39	345	13	1.16	<5	10	<10	100	1357	6	26	<10	5	18
189880	1360692	0.026	2	7.58	21	308	<2	<1	0.86	<4	3	31	5	0.90	<0.01	15	0.81	368	<1	50	371	37	1.46	<5	6	<10	108	1587	6	29	<10	5	61
189881	1360693	0.060	2	6.44	19	310	<2	<1	0.55	<4	4	31	2	0.94	<0.01	9	0.81	388	<1	52	395	22	1.14	<5	14	<10	98	1655	<2	30	<10	5	53
189882	1360694	0.013	2	6.66	22	272	<2	1	1.60	<4	5	32	4	1.57	0.02	13	1.15	733	<1	55	394	12	1.28	<5	6	<10	135	1619	8	31	<10	5	17
189883R	1360694	0.009	2	5.96	22	265	<2	2	1.59	<4	5	36	5	1.66	<0.01	11	1.17	785	1	58	389	8	1.34	<5	13	<10	130	1562	7	29	<10	5	21
189884	1360695	0.012	3	6.09	30	363	<2	<1	1.85	<4	4	27	11	1.76	<0.01	11	1.02	720	<1	44	381	28	1.46	<5	<5	<10	171	1434	<2	26	<10	6	29
189885	1360696	0.009	3	6.98	31	363	2	<1	2.08	<4	6	27	13	1.99	<0.01	14	1.17	819	<1	46	423	31	1.58	6	<5	<10	180	1569	<2	28	<10	6	37
189886	1360697	0.106	6	5.38	45	414	<2	<1	0.91	<4	6	32	15	1.84	<0.01	9	0.82	531	<1	43	427	69	1.96	<5	<5	<10	149	1600	4	34	<10	7	127
189887	1360698	0.016	3	6.30	30	384	2	2	2.80	<4	6	23	9	2.10	<0.01	10	1.34	753	<1	42	414	20	1.89	<5	<5	<10	235	1515	3	29	<10	6	303
189888	1360699	0.014	2	4.36	27	428	<2	<1	1.83	<4	6	23	11	2.93	<0.01	7	1.00	657	<1	39	400	36	3.03	<5	<5	<10	191	1478	<2	31	<10	6	86
189889	1360700	1.791	1	4.08	16	415	<2	<1	2.17	<4	15	49	33	3.81	<0.01	4	1.45	716	<1	32	647	6	0.62	<5	<5	<10	261	2691	<2	120	17	16	50
189890	1360701	0.006	2	4.55	28	349	<2	<1	1.22	<4	5	25	15	2.18	<0.01	7	0.58	402	<1	32	408	22	2.63	<5	10	<10	174	1498	6	30	<10	6	478
189891	1360702	0.006	2	4.10	33	261	<2	<1	1.52	<4	5	30	4	1.89	<0.01	8	0.58	541	<1	54	367	23	2.18	<5	7	<10	172	1293	2	25	<10	5	36
189892	1360703	0.012	2	4.24	28	254	<2	<1	2.54	<4	5	26	6	2.19	<0.01	2	0.75	1093	<1	45	295	21	2.29	<5	<5	<10	206	1100	8	22	<10	5	27
189893	1360704	0.010	2	5.27	28	256	<2	<1	1.68	<4	4	27	3	1.89	<0.01	7	0.69	387	<1	47	372	26	2.37	<5	7	<10	217	1297	11	26	<10	5	24
189894D	1360704	0.009	2	6.19	25	276	<2	<1	1.85	<4	5	31	3	2.05	<0.01	10	0.73	398	<1	53	405	27	2.54	<5	5	<10	235	1420	4	27	<10	6	29
189895	1360705	0.006	2	6.68	21	321	<2	<1	1.97	<4	7	27	5	1.64	<0.01	12	0.84	360	<1	49	427	15	2.14	<5	12	<10	241	1476	3	31	<10	6	28
189896	1360706	0.011	2	5.61	26	319	2	5	1.65	<4	6	26	4	1.96	<0.01	13	1.08	412	<1	46	393	16	2.33	<5	<5	<10	225	1440	6	29	<10	5	39
189897	1360707	0.009	2	5.32	23	303	<2	<1	1.56	<4	5	23	3	1.56	<0.01	9	0.74	240	<1	39	398	13	2.10	<5	5	<10	181	1194	3	28	<10	5	15

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, August 9, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/05/2012
 Date Completed: 07/20/2012
 Job #: 201242541
 Reference: TL 12 260
 Sample #: 125

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
189898	1360708	0.013	2	4.32	46	521	2	1	0.63	<4	13	90	34	2.59	<0.01	8	0.63	391	<1	75	451	19	2.59	<5	7	<10	193	1671	3	62	<10	10	45
189899	1360709	0.039	2	4.99	26	536	2	5	1.25	<4	19	135	44	3.71	<0.01	16	1.31	651	<1	95	523	15	1.90	5	7	<10	256	2146	3	82	<10	12	70
189900	1360710	0.008	1	4.12	15	364	<2	<1	2.13	<4	13	48	23	3.28	<0.01	4	1.35	636	<1	28	596	5	0.66	<5	<5	<10	256	2532	12	109	16	15	40
189901	1360711	0.054	3	2.70	22	446	<2	<1	1.23	<4	6	26	20	1.58	<0.01	<1	0.76	403	<1	38	488	192	1.12	<5	8	<10	177	1360	5	30	<10	5	240
189902	1360712	0.007	2	6.12	29	444	<2	3	1.53	<4	8	35	11	2.27	<0.01	7	0.95	482	1	60	606	32	1.94	<5	8	<10	169	1889	3	38	<10	7	45
189903	1360713	0.023	2	4.48	36	262	<2	<1	0.38	<4	6	25	10	1.57	<0.01	<1	0.55	416	<1	42	486	24	1.77	<5	10	<10	75	1393	7	34	<10	6	46
189904	1360714	0.054	4	2.32	36	191	<2	<1	0.44	<4	5	26	13	1.43	<0.01	<1	0.66	539	<1	51	449	46	1.32	<5	<5	<10	64	979	3	28	<10	5	120
189905D	1360714	0.056	6	6.03	41	268	<2	<1	0.78	<4	7	33	15	1.69	<0.01	3	0.82	683	<1	59	522	59	1.72	<5	10	<10	88	1336	<2	38	<10	7	140
189906	1360715	0.107	7	5.24	34	282	<2	3	0.84	<4	5	39	28	1.68	<0.01	2	0.84	424	1	70	458	56	1.58	<5	<5	<10	75	1218	5	36	<10	6	286
189907	1360716	0.094	8	7.32	39	329	2	<1	1.24	<4	6	47	34	1.97	<0.01	8	1.09	557	3	81	550	66	1.84	6	8	<10	92	1418	10	40	<10	8	315
189908	1360717	0.074	8	6.23	43	436	2	<1	0.57	<4	7	37	13	2.08	<0.01	<1	0.58	277	2	70	546	39	2.30	5	10	<10	83	1358	<2	38	<10	7	59
189909	1360718	0.057	5	6.85	46	521	2	<1	0.41	<4	7	32	16	1.98	<0.01	1	0.54	334	<1	55	558	50	2.33	5	6	<10	97	1340	<2	40	<10	7	141
189910	1360719	0.016	3	5.82	45	477	2	<1	1.51	<4	6	41	30	1.90	<0.01	4	1.04	809	2	68	514	52	1.41	<5	5	<10	114	1383	2	36	<10	6	211
189911	1360720	4.997	71	2.17	50	471	<2	<1	1.20	23	13	33	59	3.46	<0.01	<1	0.92	536	<1	25	590	631	0.83	40	5	240	228	1883	4	95	42	13	1960
189912	1360721	0.014	2	5.54	37	506	<2	<1	1.47	<4	6	31	13	1.68	<0.01	3	0.98	556	<1	53	539	30	0.97	<5	7	<10	97	1675	2	38	<10	6	86
189913	1360722	0.019	2	5.13	34	386	2	<1	1.45	<4	5	31	13	1.57	<0.01	1	0.99	588	<1	53	493	47	1.22	<5	7	<10	105	1218	5	34	<10	6	56
189914	1360723	0.851	3	2.74	57	342	<2	<1	<0.01	<4	5	31	41	1.58	<0.01	<1	0.31	<100	<1	56	451	198	1.84	<5	<5	<10	63	917	<2	30	10	4	762
189915	1360724	2.009	16	3.19	200	306	<2	<1	<0.01	4	4	38	185	1.58	<0.01	<1	0.44	<100	2	72	436	394	1.87	54	<5	<10	67	908	<2	32	12	5	958
189916D	1360724	1.860	13	1.49	178	246	<2	<1	<0.01	<4	3	28	159	1.36	<0.01	<1	0.37	<100	<1	56	370	344	1.61	46	5	<10	54	735	<2	27	11	4	823
189917	1360725	1.327	5	1.41	79	243	<2	<1	<0.01	<4	4	29	32	1.44	<0.01	<1	0.43	173	<1	56	417	113	1.57	7	7	<10	53	731	<2	26	<10	4	235

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, August 9, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/05/2012
 Date Completed: 07/20/2012
 Job #: 201242541
 Reference: TL 12 260
 Sample #: 125

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
189918	1360726	0.122	1	2.87	55	313	<2	<1	0.01	<4	4	43	23	1.65	<0.01	<1	0.49	187	3	80	445	54	1.72	<5	7	<10	57	935	<2	31	<10	5	143
189919	1360727	0.335	2	2.85	64	313	2	1	0.32	<4	5	40	22	1.82	<0.01	<1	0.68	387	3	77	427	72	1.88	<5	8	<10	62	970	5	30	<10	5	182
189920	1360728	0.608	3	3.88	93	358	2	<1	0.23	<4	6	34	54	1.96	<0.01	<1	0.55	239	1	62	458	123	2.15	<5	<5	<10	62	1353	2	33	11	6	372
189921	1360729	0.289	5	4.66	53	350	2	<1	1.12	<4	6	45	20	1.98	<0.01	2	1.04	514	2	83	488	172	1.75	6	7	<10	83	1475	14	35	<10	6	374
189922	1360730	0.008	1	0.27	15	257	3	3	1.72	4	15	44	27	3.25	<0.01	<1	1.27	615	<1	28	586	7	0.35	<5	<5	<10	175	2127	8	108	<10	16	171
189923	1360731	0.070	2	5.61	49	356	<2	<1	0.66	<4	6	30	8	1.73	<0.01	4	0.70	303	<1	52	513	18	1.83	<5	<5	<10	74	1805	<2	37	<10	7	65
189924	1360732	0.034	3	7.59	46	437	2	<1	2.51	<4	7	37	14	2.04	<0.01	9	1.29	684	<1	65	410	35	1.42	5	8	<10	121	1858	12	35	<10	7	67
189925	1360733	0.103	2	5.06	49	294	2	<1	1.46	<4	12	94	28	2.85	<0.01	5	1.19	532	3	96	462	26	2.09	6	<5	<10	83	1853	<2	57	<10	11	53
189926	1360734	0.047	2	6.46	20	346	2	<1	1.14	<4	19	134	69	3.53	<0.01	11	1.30	535	<1	97	487	32	2.11	<5	7	<10	84	2268	7	86	<10	15	78
189927D	1360734	0.048	2	6.30	19	354	2	<1	1.16	<4	19	138	73	3.66	<0.01	11	1.34	556	<1	106	503	30	2.13	<5	5	<10	83	2311	<2	87	<10	15	81
189928	1360735	0.527	3	5.27	49	271	2	<1	1.11	<4	7	40	90	1.88	<0.01	5	0.84	468	<1	55	421	82	2.00	<5	<5	<10	77	1395	<2	32	11	7	855
189929	1360736	0.179	3	4.95	56	278	<2	<1	0.97	<4	6	39	179	2.01	<0.01	4	0.77	425	2	63	424	88	2.17	6	5	<10	73	1421	3	31	13	7	894
189930	1360737	0.260	3	7.48	44	401	2	<1	1.49	<4	7	47	62	1.85	<0.01	17	0.94	500	4	68	464	143	2.23	8	6	<10	109	1880	<2	41	10	7	352
189931	1360738	1.540	8	1.33	59	310	2	<1	0.45	28	7	39	69	1.75	<0.01	<1	0.61	364	1	71	422	2641	1.95	15	<5	<10	49	1301	10	28	52	4	7859
189932	1360739	0.040	2	6.20	31	471	2	<1	2.22	<4	7	50	24	1.99	<0.01	7	1.38	796	<1	68	559	72	1.15	<5	<5	<10	101	1783	10	40	<10	7	121
189933	1360740	0.261	1	<0.01	435	>5000	<2	6	0.67	<4	5	13	32	2.86	<0.01	<1	0.21	<100	6	11	<100	53	1.04	18	9	<10	100	571	<2	15	40	8	120
189934	1360741	1.065	2	2.82	99	436	2	<1	0.26	<4	17	137	45	3.00	<0.01	<1	0.61	312	2	107	555	108	2.59	<5	<5	<10	53	1679	<2	70	<10	12	126
189935	1360742	0.874	3	4.76	177	277	2	<1	<0.01	6	14	127	115	3.51	<0.01	1	0.41	109	2	100	480	304	4.23	10	<5	<10	53	1472	<2	80	15	10	1382
189936	1360743	2.197	7	6.11	430	263	2	<1	0.03	24	16	136	248	4.28	<0.01	5	0.43	123	5	119	462	1819	5.64	104	5	<10	62	1370	<2	78	58	11	8571
189937	1360744	0.385	3	4.45	142	290	2	1	0.34	<4	17	139	76	3.21	<0.01	<1	0.64	228	3	111	524	158	3.53	<5	<5	<10	65	1437	2	78	<10	12	411

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, August 9, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/05/2012
 Date Completed: 07/20/2012
 Job #: 201242541
 Reference: TL 12 260
 Sample #: 125

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
189938D	1360744	0.420	3	8.60	117	292	2	<1	0.72	<4	15	122	64	2.80	<0.01	15	0.74	212	2	90	475	109	3.69	5	5	<10	95	1518	<2	75	<10	13	245
189939	1360745	0.125	2	6.33	37	297	2	<1	0.80	<4	15	123	68	2.39	<0.01	7	0.79	322	2	86	467	41	2.22	<5	7	<10	77	1648	8	71	<10	13	53
189940	1360746	0.138	3	8.47	56	391	2	1	0.40	<4	17	149	55	2.60	<0.01	13	0.64	194	6	110	542	76	2.69	6	<5	<10	74	2239	4	80	<10	15	94
189941	1360747	0.395	3	4.28	80	247	2	1	0.57	<4	12	93	40	2.25	<0.01	5	0.70	290	<1	66	376	221	2.53	5	<5	<10	75	1470	<2	55	<10	10	270
189942	1360748	0.098	2	6.89	48	479	2	<1	0.56	<4	15	117	33	2.35	<0.01	10	0.74	310	3	92	507	86	2.36	<5	5	<10	81	2196	2	76	11	12	142
189943	1360749	0.031	2	7.40	13	473	4	4	1.43	<4	9	66	24	2.11	<0.01	16	0.99	540	<1	65	480	27	1.78	<5	<5	14	106	2065	2	51	<10	9	90
189944	1360750	0.011	1	6.94	14	441	<2	<1	2.52	<4	14	51	25	3.52	<0.01	11	1.49	696	<1	31	652	8	0.96	6	8	<10	303	3056	4	119	18	18	44
189945	1360751	0.018	2	7.87	12	533	2	<1	1.59	<4	13	110	45	2.78	<0.01	15	1.17	551	1	70	544	47	1.97	<5	11	<10	130	2193	3	58	<10	11	238
189946	1360752	1.019	2	4.92	22	491	2	2	1.32	<4	7	45	39	2.07	<0.01	6	1.04	468	3	75	525	43	1.45	<5	6	<10	114	1799	4	38	10	6	338
189947	1360753	0.033	1	5.86	20	497	2	<1	1.80	<4	7	121	16	1.93	<0.01	10	1.29	473	1	63	545	22	1.43	<5	6	<10	125	1727	<2	38	10	6	77
189948	1360754	0.061	3	6.06	20	488	2	<1	1.50	<4	8	37	270	2.20	<0.01	10	1.14	446	2	61	513	36	1.85	<5	<5	<10	120	1836	3	38	12	7	582
189949R	1360754	0.079	2	4.62	17	476	2	1	1.27	<4	7	37	200	2.10	<0.01	6	1.04	420	2	65	485	27	1.64	<5	5	<10	109	1724	4	36	11	6	494
189950	1360755	0.043	4	5.95	19	445	2	<1	2.66	7	6	37	427	2.29	<0.01	9	1.59	546	4	61	494	25	1.71	<5	7	<10	134	1739	4	37	25	7	1921
189951	1360756	0.030	2	4.97	20	443	2	<1	2.05	10	5	37	220	2.15	<0.01	5	1.25	450	6	64	489	25	1.52	<5	9	<10	132	1748	2	35	26	6	2614
189952	1360757	0.054	1	5.72	19	481	2	<1	1.87	<4	7	40	14	1.94	<0.01	10	1.17	470	<1	68	565	78	1.10	<5	7	<10	123	1830	<2	38	10	6	275
189953	1360758	1.649	12	4.44	56	485	2	<1	0.32	28	8	30	363	2.35	<0.01	7	0.57	210	<1	51	472	1033	3.01	46	5	<10	75	1834	<2	35	61	5	7370
189954	1360759	0.036	1	7.60	20	598	2	4	2.16	<4	9	42	31	2.12	<0.01	16	1.27	511	3	71	621	34	1.20	<5	5	<10	149	2096	<2	42	<10	8	183

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, July 30, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 06/25/2012
 Date Completed: 07/10/2012
 Job #: 201242318
 Reference: TL 12-261
 Sample #: 84

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
178482	1360760	1.861	1	8.55	7	474	<2	2	2.65	<4	17	60	31	3.77	0.02	25	1.56	722	<1	38	625	10	0.32	<5	<5	<10	316	3204	<2	124	27	18	55
178483	1360761	0.038	<1	6.04	24	437	<2	28	1.58	<4	8	30	14	2.34	<0.01	20	1.06	669	<1	44	536	22	1.44	<5	5	<10	225	2233	<2	42	<10	7	81
178484	1360762	<0.005	<1	6.24	10	452	<2	11	1.23	<4	5	28	3	0.54	<0.01	13	0.51	183	<1	36	393	24	0.25	<5	<5	<10	237	1495	<2	28	<10	5	37
178485	1360763	0.007	<1	6.75	<2	427	<2	18	1.61	<4	5	31	5	0.51	<0.01	15	0.49	175	2	48	357	27	0.25	<5	10	<10	275	1441	<2	28	<10	5	58
178486	1360764	0.010	<1	6.31	<2	447	<2	14	1.69	<4	6	36	8	0.62	<0.01	13	0.58	209	2	49	375	23	0.29	<5	<5	<10	264	1472	<2	28	<10	5	23
178487	1360765	0.006	<1	6.07	<2	410	<2	17	1.94	<4	5	36	7	0.58	<0.01	10	0.53	202	7	54	383	23	0.23	<5	<5	<10	270	1372	<2	28	<10	5	17
178488	1360766	0.008	<1	5.66	6	540	<2	19	1.39	<4	7	29	6	0.69	<0.01	13	0.54	190	<1	36	389	26	0.34	<5	<5	<10	277	1608	<2	31	<10	5	32
178489	1360767	<0.005	<1	5.55	4	513	<2	16	1.24	<4	7	31	6	0.69	0.04	14	0.50	150	2	52	355	12	0.30	<5	5	<10	252	1478	<2	28	<10	5	19
178490	1360768	0.017	<1	6.41	2	613	<2	19	1.66	<4	7	30	16	1.11	<0.01	18	0.71	283	2	40	428	18	0.51	<5	6	<10	281	1686	<2	34	<10	6	50
178491	1360769	0.010	<1	6.20	13	576	<2	17	1.27	<4	6	35	8	0.71	<0.01	15	0.50	167	2	51	366	18	0.28	<5	6	<10	244	1583	<2	32	<10	5	23
178492D	1360769	0.010	<1	8.15	6	626	<2	24	1.51	<4	6	34	8	0.71	0.04	22	0.57	169	2	46	364	19	0.33	<5	<5	<10	277	1693	<2	32	<10	6	22
178493	1360770	<0.005	1	4.45	<2	374	<2	26	2.26	<4	15	51	22	3.28	<0.01	11	1.40	648	<1	31	570	6	0.19	<5	<5	<10	265	2630	<2	110	18	16	45
178494	1360771	0.007	<1	6.65	<2	541	<2	16	1.36	<4	5	29	5	0.75	<0.01	17	0.51	179	1	40	371	21	0.30	<5	5	<10	245	1600	<2	30	<10	6	39
178495	1360772	0.028	<1	6.89	7	528	<2	16	1.76	<4	8	30	23	1.66	<0.01	18	0.67	450	<1	44	474	48	0.75	<5	<5	<10	260	2003	<2	38	<10	7	54
178496	1360773	0.090	1	6.30	12	512	<2	15	1.87	<4	8	39	42	1.95	<0.01	16	0.80	628	3	55	462	254	1.13	<5	<5	<10	253	1773	<2	36	<10	7	416
178497	1360774	0.017	<1	5.77	5	468	2	18	1.99	<4	8	38	11	1.91	<0.01	15	0.82	590	1	49	455	44	0.83	<5	<5	<10	227	1744	<2	36	<10	7	55
178498	1360775	0.008	<1	5.84	<2	396	<2	16	1.73	<4	5	60	7	1.38	<0.01	14	0.70	432	6	67	332	15	0.43	<5	<5	<10	145	1502	<2	28	<10	7	42
178499	1360776	0.146	<1	4.83	<2	389	<2	18	1.61	<4	5	75	8	1.50	<0.01	10	0.67	448	8	99	332	16	0.39	<5	<5	<10	135	1421	3	27	<10	6	50
178500	1360777	0.020	<1	7.36	38	543	2	12	1.07	<4	10	41	8	1.40	<0.01	16	0.73	381	3	58	477	18	0.90	<5	9	<10	137	2073	<2	37	<10	7	186
178501	1360778	0.025	<1	5.38	13	452	<2	19	0.93	<4	9	56	13	1.01	0.04	10	0.62	320	5	78	441	39	0.41	<5	<5	<10	118	1746	<2	36	21	7	55

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By:  Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Monday, July 30, 2012

Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/25/2012
 Date Completed: 07/10/2012
 Job #: 201242318
 Reference: TL 12-261
 Sample #: 84

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
178502	1360779	0.011	<1	6.26	7	456	<2	20	1.59	<4	5	44	17	1.48	<0.01	16	1.02	575	2	53	406	38	0.82	<5	<5	<10	137	1477	<2	29	<10	6	95
178503D	1360779	0.013	1	5.37	14	434	<2	10	1.42	<4	6	58	17	1.52	<0.01	14	0.96	561	6	79	384	37	0.78	<5	<5	<10	122	1382	<2	28	<10	6	92
178504	1360780	4.778	71	5.20	35	477	<2	8	1.49	19	14	37	50	3.15	<0.01	13	0.96	499	1	26	535	569	0.53	65	<5	225	250	2032	<2	90	56	14	1748
178505	1360781	0.026	1	4.22	21	396	<2	17	0.85	<4	4	58	7	1.10	<0.01	10	0.65	263	7	74	332	30	0.71	<5	5	<10	93	1152	<2	23	11	6	58
178506	1360782	0.020	<1	6.12	24	595	<2	14	1.04	<4	6	44	5	1.28	<0.01	13	0.85	330	3	61	341	22	0.90	<5	<5	<10	101	1553	<2	29	<10	6	67
178507	1360783	0.088	1	6.49	52	530	2	17	1.18	<4	6	39	15	1.53	<0.01	18	0.85	405	2	58	348	43	1.10	<5	<5	11	105	1557	<2	27	<10	6	133
178508	1360784	0.022	<1	6.27	19	474	<2	5	1.66	<4	5	47	11	1.37	<0.01	14	0.79	396	5	69	346	11	0.80	<5	6	<10	118	1349	<2	27	<10	6	32
178509	1360785	0.015	<1	7.35	9	591	2	19	2.01	<4	5	39	15	1.35	<0.01	15	0.87	422	3	55	390	21	0.71	<5	<5	10	152	1449	<2	28	<10	6	32
178510	1360786	0.032	2	8.40	30	625	<2	10	1.43	<4	9	43	36	1.48	<0.01	22	0.90	416	4	71	515	63	0.95	<5	<5	<10	158	2018	<2	35	<10	7	228
178511	1360787	0.037	3	6.38	18	490	<2	18	1.27	<4	6	39	20	1.00	<0.01	18	0.95	523	3	62	564	295	0.54	<5	<5	<10	136	1860	<2	31	14	6	915
178512	1360788	0.096	1	5.93	25	443	<2	34	1.28	<4	6	36	25	1.31	<0.01	16	1.00	484	3	60	478	119	0.96	<5	<5	<10	130	1818	<2	30	<10	6	201
178513	1360789	0.119	1	6.04	32	467	<2	21	1.44	<4	6	39	7	1.39	0.28	20	1.14	751	4	60	472	56	1.03	<5	<5	<10	139	1737	4	30	<10	7	372
178514D	1360789	0.061	1	6.46	25	490	<2	8	1.52	<4	6	38	7	1.41	0.23	20	1.17	765	3	55	490	56	1.02	<5	6	<10	148	1772	<2	31	11	7	381
178515	1360790	<0.005	<1	5.03	12	382	<2	13	2.28	<4	15	51	27	3.20	0.03	12	1.39	644	<1	28	568	14	0.21	<5	8	<10	275	2670	3	108	21	16	96
178516	1360791	0.046	1	7.52	16	710	2	26	2.04	<4	6	45	16	1.63	<0.01	21	1.19	574	3	55	589	44	0.87	<5	5	<10	209	2011	<2	37	10	8	54
178517	1360792	0.032	<1	5.40	12	448	<2	7	1.28	<4	4	35	6	0.94	<0.01	12	0.60	358	3	54	349	34	0.59	<5	<5	<10	153	1414	<2	29	<10	5	29
178518	1360793	0.033	<1	5.87	32	478	<2	18	1.19	<4	7	40	16	1.66	<0.01	14	0.81	720	1	55	415	41	1.44	<5	<5	<10	141	1742	<2	36	<10	7	55
178519	1360794	0.046	1	5.87	26	410	<2	18	1.02	<4	5	31	24	1.21	<0.01	14	0.86	581	2	46	351	54	0.93	<5	<5	<10	125	1603	<2	28	<10	6	211
178520	1360795	0.224	<1	6.96	27	503	<2	15	0.83	<4	5	39	14	1.17	<0.01	16	0.74	383	2	48	341	30	0.83	<5	<5	<10	117	1646	<2	28	<10	6	37
178521	1360796	0.066	<1	7.46	30	497	<2	12	0.89	<4	5	34	13	1.18	<0.01	18	0.77	376	2	41	344	21	0.88	<5	<5	<10	121	1650	<2	28	<10	6	34

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By:  Derek Demianuk H.Bsc., Laboratory Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Monday, July 30, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/25/2012
 Date Completed: 07/10/2012
 Job #: 201242318
 Reference: TL 12-261
 Sample #: 84

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
178522	1360797	0.022	<1	5.98	14	367	2	14	1.29	<4	4	30	4	1.12	0.02	15	0.84	488	2	39	342	20	0.67	<5	<5	<10	134	1561	<2	27	<10	5	24
178523	1360798	0.021	<1	6.83	17	312	<2	18	1.49	<4	4	32	3	1.22	0.02	17	0.85	487	2	42	360	17	0.80	<5	9	13	123	1552	<2	27	<10	6	21
178524	1360799	0.150	<1	6.60	19	377	2	18	0.75	<4	6	34	3	1.42	<0.01	16	0.74	388	1	45	345	17	1.21	<5	6	<10	98	1664	<2	29	<10	6	22
178525D	1360799	0.117	<1	6.63	22	373	<2	16	0.76	<4	5	33	3	1.42	<0.01	16	0.74	387	2	46	359	18	1.21	<5	<5	<10	99	1650	<2	29	<10	6	23
178526	1360800	0.239	1	1.13	408	>5000	<2	19	0.90	<4	6	20	28	2.72	<0.01	7	0.28	<100	9	13	<100	21	0.55	14	<5	<10	118	840	5	15	46	8	20
178527	1360801	0.072	1	4.76	23	384	<2	16	0.39	<4	4	32	10	1.08	0.03	9	0.55	258	2	45	312	50	0.88	<5	5	<10	72	1418	<2	24	<10	5	130
178528	1360802	15.969	2	6.69	16	353	<2	27	1.49	<4	5	38	4	1.44	<0.01	19	1.06	545	2	47	348	23	1.01	<5	6	<10	109	1558	<2	26	<10	6	27
178529	1360803	0.101	1	5.95	11	313	<2	2	1.41	<4	5	42	7	1.28	<0.01	17	1.04	612	4	64	336	23	0.52	<5	<5	<10	108	1495	<2	26	<10	5	40
178530	1360804	0.768	<1	5.89	28	285	<2	10	1.42	<4	6	35	7	1.65	<0.01	17	1.01	715	2	52	353	27	1.07	<5	<5	<10	115	1529	<2	27	<10	6	88
178531	1360805	0.017	1	7.57	22	321	<2	10	1.55	<4	8	36	18	1.85	<0.01	18	1.14	779	<1	46	514	30	1.02	<5	<5	<10	112	1807	<2	38	<10	8	86
178532	1360806	0.093	4	9.17	30	442	2	12	1.15	<4	8	42	8	1.61	<0.01	20	0.81	565	3	51	511	51	1.23	<5	9	<10	121	1704	<2	40	<10	8	105
178533	1360807	0.436	13	5.71	36	432	<2	17	0.04	<4	7	40	19	1.62	0.02	4	0.32	<100	2	51	430	79	1.61	<5	6	<10	82	1187	<2	36	10	6	420
178534	1360808	0.256	5	7.34	43	535	2	7	0.67	<4	7	44	24	1.66	<0.01	14	0.76	261	3	52	479	139	1.36	<5	<5	<10	108	1279	<2	38	<10	7	128
178535	1360809	0.661	3	5.71	35	497	<2	23	0.10	<4	5	39	35	1.29	<0.01	6	0.35	<100	2	50	393	147	1.26	8	7	<10	90	1107	<2	34	12	6	350
178536D	1360809	0.619	4	8.31	36	553	2	12	0.32	<4	6	46	36	1.39	<0.01	15	0.45	<100	3	53	419	156	1.39	9	<5	<10	111	1276	<2	37	13	7	357
178537	1360810	0.012	<1	4.67	11	383	<2	21	2.32	<4	16	54	22	3.35	<0.01	11	1.43	667	<1	31	584	13	0.20	<5	<5	<10	273	2741	<2	113	22	16	49
178538	1360811	0.669	7	7.19	69	520	2	19	0.20	<4	7	34	75	1.67	<0.01	10	0.44	<100	2	45	438	151	1.68	13	<5	<10	89	1367	<2	36	13	7	282
178539	1360812	0.161	<1	6.50	56	470	<2	14	1.06	<4	8	31	19	1.77	<0.01	12	0.88	355	<1	42	478	69	1.42	<5	7	<10	99	1456	<2	32	10	7	106
178540	1360813	0.235	1	6.28	45	411	2	15	1.58	<4	7	33	19	1.87	<0.01	12	1.14	555	<1	44	465	61	1.40	<5	<5	<10	104	1380	<2	32	<10	7	84
178541	1360814	0.080	<1	6.17	43	447	2	21	0.99	<4	8	37	24	1.54	<0.01	10	0.80	354	2	51	464	61	1.15	<5	<5	<10	94	1477	<2	34	<10	7	73

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By:  Derek Demianuk H.Bsc., Laboratory Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Monday, July 30, 2012

Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/25/2012
 Date Completed: 07/10/2012
 Job #: 201242318
 Reference: TL 12-261
 Sample #: 84

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
178542	1360815	4.219	11	4.55	81	326	2	18	0.31	7	5	41	136	2.04	0.07	4	0.45	129	7	61	397	331	2.08	20	<5	<10	77	1128	<2	29	29	7	2089
178543	1360816	3.491	10	5.62	77	382	<2	20	0.28	9	5	38	69	1.73	0.02	6	0.50	144	5	55	407	238	1.78	19	5	<10	80	1300	<2	33	45	7	3397
178544	1360817	0.325	3	7.04	48	455	2	24	0.57	8	7	35	36	1.58	<0.01	11	0.71	231	5	55	442	163	1.48	<5	<5	<10	95	1465	<2	34	28	8	1829
178545	1360818	0.727	7	6.53	48	430	2	18	0.99	<4	7	38	38	1.50	0.01	11	0.89	361	4	51	447	255	1.24	<5	5	<10	112	1379	<2	33	12	8	476
178546	1360819	0.414	5	7.59	49	444	2	12	0.43	<4	7	37	30	1.67	<0.01	13	0.61	153	5	52	438	146	1.60	5	8	<10	90	1659	<2	36	<10	9	284
178547R	1360819	0.418	6	9.84	58	481	2	11	0.68	<4	8	41	36	1.76	<0.01	21	0.73	166	8	56	462	174	1.73	7	9	12	111	1792	<2	38	12	11	284
178548	1360820	1.932	1	5.27	15	419	<2	27	2.31	<4	17	52	37	3.72	<0.01	12	1.48	710	<1	35	613	19	0.23	<5	<5	<10	276	2794	3	118	24	17	129
178549	1360821	0.050	2	6.28	31	366	2	10	0.93	<4	7	39	16	1.59	<0.01	10	0.77	273	5	57	471	56	1.21	<5	5	<10	106	1635	<2	35	<10	8	69
178550	1360822	0.200	2	5.89	56	391	2	20	0.59	<4	7	35	11	1.62	<0.01	8	0.58	186	4	48	417	28	1.40	<5	7	<10	84	1707	<2	34	14	7	387
178551	1360823	0.062	2	6.68	45	388	<2	14	1.66	<4	7	38	5	1.56	<0.01	14	1.10	495	2	50	481	33	0.95	<5	<5	<10	118	1616	4	32	<10	8	83
178552	1360824	0.078	2	6.92	40	419	<2	14	1.04	<4	8	28	3	1.67	<0.01	14	0.81	303	1	43	478	23	1.29	<5	6	<10	100	1837	<2	35	<10	8	36
178553	1360825	0.051	2	7.57	28	453	2	25	2.02	<4	7	33	4	1.60	<0.01	17	1.25	683	3	43	456	43	0.83	<5	<5	<10	126	1705	<2	33	<10	9	58
178554	1360826	0.060	2	7.87	20	379	2	17	1.72	<4	8	26	7	1.80	<0.01	20	1.23	527	2	39	485	31	0.85	<5	5	14	124	1853	<2	35	11	10	105
178555	1360827	0.080	2	6.50	35	395	<2	13	1.26	<4	7	39	19	1.61	<0.01	15	0.98	454	4	59	461	58	1.01	<5	<5	<10	99	1579	<2	31	<10	9	146
178556	1360828	0.193	3	7.51	36	457	<2	17	1.44	<4	8	39	43	1.76	<0.01	18	1.01	435	5	58	479	86	1.31	<5	8	<10	107	1733	<2	33	10	10	127
178557	1360829	0.073	2	8.36	23	520	2	9	1.51	<4	7	38	17	1.43	<0.01	20	1.00	482	3	51	486	39	0.87	<5	<5	<10	113	1792	<2	35	<10	10	124
178558D	1360829	0.115	3	9.79	22	563	2	11	1.66	<4	7	38	17	1.47	<0.01	24	1.07	500	4	50	503	40	0.92	<5	<5	<10	124	1916	<2	38	<10	11	121
178559	1360830	0.009	1	5.74	5	415	<2	10	2.47	<4	16	54	22	3.38	<0.01	11	1.46	683	<1	33	596	7	0.22	<5	<5	<10	299	2923	4	116	21	18	46
178560	1360831	0.122	2	6.30	22	392	<2	25	1.86	<4	16	137	36	2.86	<0.01	15	1.23	700	5	105	497	30	1.07	5	<5	<10	109	2141	<2	64	<10	16	76
178561	1360832	0.310	2	5.23	61	299	2	19	1.27	<4	15	114	37	2.63	<0.01	11	0.95	501	3	81	486	49	1.71	<5	<5	<10	85	1833	<2	62	<10	14	72

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By:  Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Monday, July 30, 2012

Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/25/2012
 Date Completed: 07/10/2012
 Job #: 201242318
 Reference: TL 12-261
 Sample #: 84

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
178562	1360833	0.249	2	5.75	55	456	2	13	0.30	<4	7	55	75	2.49	<0.01	11	0.53	158	9	80	442	144	2.19	<5	<5	<10	71	1637	<2	40	14	8	526
178563	1360834	0.415	4	7.06	61	474	2	17	0.26	<4	8	48	87	1.79	<0.01	13	0.50	<100	8	72	436	311	1.67	<5	<5	<10	77	1665	<2	36	15	8	540
178564	1360835	0.183	2	5.60	31	511	<2	23	0.49	<4	6	40	29	1.39	<0.01	9	0.60	226	4	59	445	41	1.08	<5	7	<10	74	1667	<2	36	14	7	124
178565	1360836	0.183	2	6.97	25	545	2	23	0.53	<4	7	59	28	1.54	<0.01	13	0.63	226	10	90	453	38	1.16	<5	8	<10	82	1742	<2	38	<10	9	172
178566	1360837	0.074	2	8.08	46	537	2	10	1.43	<4	6	48	27	1.66	<0.01	19	0.96	399	7	75	493	39	0.97	<5	<5	<10	114	1764	<2	38	10	10	137
178567	1360838	0.035	2	7.83	5	429	2	12	1.85	<4	7	41	13	1.68	<0.01	20	1.13	438	4	58	507	35	0.71	<5	<5	<10	126	1805	<2	35	<10	10	277
178568	1360839	0.044	2	8.22	14	497	2	8	2.47	<4	8	36	4	1.86	<0.01	20	1.38	422	4	53	527	22	0.55	<5	<5	<10	152	1772	<2	36	<10	10	54
178569D	1360839	0.017	1	7.95	6	499	2	16	2.42	<4	8	38	3	1.85	<0.01	19	1.35	415	3	60	510	22	0.54	<5	<5	<10	148	1914	<2	37	<10	9	49
178570	1360840	4.837	75	4.52	38	467	<2	13	1.46	19	14	34	50	3.20	<0.01	9	0.95	506	2	27	533	581	0.53	66	5	230	246	1950	<2	90	61	15	1781
178571	1360841	0.042	2	7.67	8	510	<2	27	2.55	<4	7	34	4	1.81	<0.01	17	1.40	444	3	51	499	39	0.50	<5	<5	11	164	1722	<2	35	<10	9	56
178572	1360842	0.007	2	6.25	5	449	2	3	1.31	<4	7	40	44	1.94	<0.01	14	0.90	306	3	55	461	66	0.95	<5	6	<10	123	1694	<2	34	11	8	278
178573	1360843	0.009	2	7.90	2	533	2	17	2.57	<4	7	36	10	1.83	<0.01	18	1.46	506	4	56	519	38	0.58	<5	7	<10	195	1891	8	37	<10	9	73

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By:  Derek Demianliuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Tuesday, July 10, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/25/2012
 Date Completed: 07/10/2012
 Job #: 201242318
 Reference: TL 12-261
 Sample #: 84

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
178482	1360760	1861	0.054	1.861
178483	1360761	38	0.001	0.038
178484	1360762	<5	<0.001	<0.005
178485	1360763	7	<0.001	0.007
178486	1360764	10	<0.001	0.010
178487	1360765	6	<0.001	0.006
178488	1360766	8	<0.001	0.008
178489	1360767	<5	<0.001	<0.005
178490	1360768	17	<0.001	0.017
178491	1360769	10	<0.001	0.010
178492 Dup	1360769	10	<0.001	0.010
178493	1360770	<5	<0.001	<0.005
178494	1360771	7	<0.001	0.007
178495	1360772	28	<0.001	0.028
178496	1360773	90	0.003	0.090
178497	1360774	17	<0.001	0.017
178498	1360775	8	<0.001	0.008
178499	1360776	146	0.004	0.146
178500	1360777	20	<0.001	0.020
178501	1360778	25	<0.001	0.025
178502	1360779	11	<0.001	0.011
178503 Dup	1360779	13	<0.001	0.013
178504	1360780	4778	0.139	4.778
178505	1360781	26	<0.001	0.026
178506	1360782	20	<0.001	0.020
178507	1360783	88	0.003	0.088
178508	1360784	22	<0.001	0.022
178509	1360785	15	<0.001	0.015
178510	1360786	32	<0.001	0.032
178511	1360787	37	0.001	0.037

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Tuesday, July 10, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/25/2012
 Date Completed: 07/10/2012
 Job #: 201242318
 Reference: TL 12-261
 Sample #: 84

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
178512	1360788	96	0.003	0.096
178513	1360789	119	0.003	0.119
178514 Dup	1360789	61	0.002	0.061
178515	1360790	<5	<0.001	<0.005
178516	1360791	46	0.001	0.046
178517	1360792	32	<0.001	0.032
178518	1360793	33	<0.001	0.033
178519	1360794	46	0.001	0.046
178520	1360795	224	0.007	0.224
178521	1360796	66	0.002	0.066
178522	1360797	22	<0.001	0.022
178523	1360798	21	<0.001	0.021
178524	1360799	150	0.004	0.150
178525 Dup	1360799	117	0.003	0.117
178526	1360800	239	0.007	0.239
178527	1360801	72	0.002	0.072
178528	1360802	15969	0.466	15.969
178529	1360803	101	0.003	0.101
178530	1360804	768	0.022	0.768
178531	1360805	17	<0.001	0.017
178532	1360806	93	0.003	0.093
178533	1360807	436	0.013	0.436
178534	1360808	256	0.007	0.256
178535	1360809	661	0.019	0.661
178536 Dup	1360809	619	0.018	0.619
178537	1360810	12	<0.001	0.012
178538	1360811	669	0.020	0.669
178539	1360812	161	0.005	0.161
178540	1360813	235	0.007	0.235
178541	1360814	80	0.002	0.080

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Tuesday, July 10, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/25/2012
 Date Completed: 07/10/2012
 Job #: 201242318
 Reference: TL 12-261
 Sample #: 84

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
178542	1360815	4219	0.123	4.219
178543	1360816	3491	0.102	3.491
178544	1360817	325	0.009	0.325
178545	1360818	727	0.021	0.727
178546	1360819	414	0.012	0.414
178547 Rep	1360819	418	0.012	0.418
178548	1360820	1932	0.056	1.932
178549	1360821	50	0.001	0.050
178550	1360822	200	0.006	0.200
178551	1360823	62	0.002	0.062
178552	1360824	78	0.002	0.078
178553	1360825	51	0.001	0.051
178554	1360826	60	0.002	0.060
178555	1360827	80	0.002	0.080
178556	1360828	193	0.006	0.193
178557	1360829	73	0.002	0.073
178558 Dup	1360829	115	0.003	0.115
178559	1360830	9	<0.001	0.009
178560	1360831	122	0.004	0.122
178561	1360832	310	0.009	0.310
178562	1360833	249	0.007	0.249
178563	1360834	415	0.012	0.415
178564	1360835	183	0.005	0.183
178565	1360836	183	0.005	0.183
178566	1360837	74	0.002	0.074
178567	1360838	35	0.001	0.035
178568	1360839	44	0.001	0.044
178569 Dup	1360839	17	<0.001	0.017
178570	1360840	4837	0.141	4.837
178571	1360841	42	0.001	0.042

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By:  Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Tuesday, July 10, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/25/2012
 Date Completed: 07/10/2012
 Job #: 201242318
 Reference: TL 12-261
 Sample #: 84

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
178572	1360842	7	<0.001	0.007
178573	1360843	9	<0.001	0.009

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Tuesday, August 28, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/20/2012
 Date Completed: 08/08/2012
 Job #: 201242759
 Reference: TL12262
 Sample #: 321

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
205894	1369088	0.010	<1	7.12	15	594	2	<1	1.12	5	25	160	44	4.27	0.16	36	1.61	554	<1	95	564	22	0.52	<5	14	<10	312	3133	<2	104	<10	17	74
205895	1369089	0.006	<1	6.19	13	539	2	<1	0.96	5	22	139	38	3.68	0.09	32	1.54	456	<1	80	508	30	0.50	5	7	<10	307	2762	5	86	<10	15	67
205896	1369090	<0.005	<1	7.55	11	564	2	<1	1.31	5	22	148	42	3.71	0.09	34	1.45	525	<1	78	508	26	0.61	<5	5	<10	360	2900	<2	89	<10	16	56
205897	1369091	<0.005	<1	7.20	6	596	2	<1	1.30	5	24	164	44	4.11	0.12	36	1.54	573	<1	115	554	26	0.57	<5	8	<10	346	3000	6	98	<10	16	68
205898	1369092	<0.005	<1	6.84	10	563	2	<1	0.49	6	31	187	49	5.21	0.10	54	1.97	466	<1	154	586	19	0.52	<5	<5	<10	179	3137	2	134	<10	17	23
205899	1369093	<0.005	<1	6.55	11	524	2	<1	0.89	6	26	167	45	4.52	0.12	40	1.72	529	<1	128	566	21	0.49	<5	11	<10	246	2894	6	110	<10	16	62
205900	1369094	<0.005	<1	6.05	14	613	2	<1	1.01	5	22	155	43	3.70	0.13	31	1.44	489	<1	124	521	28	0.55	<5	7	<10	345	2640	4	84	<10	14	62
205901	1369095	<0.005	<1	5.02	13	625	2	<1	0.92	4	21	156	42	3.65	0.22	26	1.34	517	<1	116	527	29	0.54	<5	14	<10	338	2557	<2	79	<10	14	59
205902	1369096	<0.005	<1	4.98	10	609	2	<1	0.81	5	22	165	42	3.93	0.10	29	1.44	497	<1	144	542	23	0.49	<5	8	<10	295	2563	<2	88	<10	14	65
205903	1369097	<0.005	<1	4.84	13	635	2	<1	0.88	6	25	173	43	4.35	0.09	31	1.57	534	<1	142	561	20	0.44	<5	9	<10	309	2859	4	96	<10	15	65
205904D	1369097	<0.005	<1	4.94	18	622	2	4	0.90	6	25	171	43	4.29	0.05	31	1.56	527	<1	140	559	27	0.44	5	<5	<10	311	2797	<2	94	<10	15	71
205905	1369098	<0.005	<1	6.62	9	655	2	<1	1.12	5	24	161	43	4.05	<0.01	33	1.53	515	<1	107	561	32	0.53	<5	13	<10	355	3166	2	96	<10	16	65
205906	1369099	0.005	<1	7.89	10	692	2	<1	1.41	5	24	167	43	3.87	0.03	36	1.51	541	<1	128	530	27	0.63	<5	11	<10	341	3122	<2	95	<10	17	60
205907	1369100	<0.005	<1	5.34	14	453	2	<1	2.54	5	18	58	24	3.62	0.29	9	1.50	718	<1	54	658	13	0.34	<5	9	<10	317	3189	<2	126	24	18	54
205908	1369101	<0.005	<1	6.54	13	671	2	<1	1.30	5	24	174	48	3.95	0.20	31	1.46	558	<1	119	564	29	0.64	<5	<5	<10	375	3124	7	91	<10	16	64
205909	1369102	<0.005	<1	7.87	7	672	2	<1	1.39	5	22	162	42	3.61	0.19	34	1.45	509	1	114	531	30	0.67	<5	11	<10	411	2931	6	82	<10	17	58
205910	1369103	<0.005	<1	3.72	10	624	<2	<1	0.94	5	23	171	43	3.80	0.10	27	1.60	493	<1	116	922	22	0.52	<5	10	<10	333	2711	2	83	<10	15	64
205911	1369104	0.007	<1	7.91	11	793	2	<1	1.03	6	27	176	52	4.58	0.10	40	1.79	524	<1	136	593	22	0.64	5	8	<10	252	3323	8	112	<10	17	78
205912	1369105	<0.005	<1	5.10	10	539	<2	<1	0.57	6	28	183	54	4.98	0.02	33	1.80	548	<1	143	598	18	0.45	<5	<5	<10	216	2876	4	116	<10	16	82
205913	1369106	<0.005	<1	7.65	9	569	2	<1	0.91	6	27	171	47	4.61	0.13	39	1.76	527	<1	126	565	26	0.58	<5	10	<10	262	3142	<2	113	<10	17	77

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/20/2012
 Date Completed: 08/08/2012
 Job #: 201242759
 Reference: TL12262
 Sample #: 321

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
205914	1369107	<0.005	<1	6.37	9	610	2	<1	1.14	5	23	172	44	3.89	0.16	30	1.45	517	2	134	540	25	0.59	<5	<5	<10	363	2836	3	87	<10	15	57
205915D	1369107	<0.005	<1	6.14	10	622	2	<1	1.11	5	25	177	47	4.06	0.12	30	1.50	530	1	139	566	26	0.58	<5	9	<10	360	2821	3	88	<10	15	62
205916	1369108	0.006	<1	5.22	12	578	2	<1	0.99	5	24	172	46	4.14	0.06	29	1.47	525	<1	137	570	21	0.51	<5	<5	<10	286	2722	<2	92	<10	14	66
205917	1369109	<0.005	<1	6.66	11	599	2	<1	1.27	5	23	173	44	4.07	0.24	33	1.55	546	<1	127	576	33	0.59	<5	<5	<10	361	2991	4	92	<10	16	62
205918	1369110	0.010	<1	6.92	11	636	2	<1	1.32	5	24	165	46	3.85	0.19	32	1.47	548	<1	96	540	26	0.70	<5	9	<10	351	2967	3	89	<10	17	67
205919	1369111	0.006	<1	8.36	11	665	2	<1	1.52	5	24	166	45	4.01	0.20	34	1.60	545	<1	113	555	31	0.70	<5	7	<10	373	3198	2	92	14	17	66
205920	1369112	<0.005	<1	7.77	9	679	2	<1	1.49	6	25	169	49	4.18	0.17	33	1.57	597	<1	118	580	32	0.64	<5	8	<10	380	3324	6	103	<10	18	72
205921	1369113	0.006	<1	5.60	13	585	2	<1	0.92	5	22	156	41	4.00	0.19	30	1.51	545	<1	117	538	21	0.49	<5	16	<10	299	2607	2	91	<10	16	66
205922	1369114	<0.005	<1	7.95	11	619	2	<1	1.18	6	25	163	49	4.31	0.14	39	1.64	561	<1	113	569	11	0.62	<5	5	<10	339	2961	6	103	12	18	29
205923	1369115	<0.005	<1	8.54	11	554	2	<1	0.70	5	22	154	42	3.89	0.14	42	1.68	436	<1	100	524	13	0.63	<5	7	<10	275	2646	2	95	<10	19	27
205924	1369116	<0.005	<1	7.06	9	706	2	<1	0.44	5	24	167	37	4.51	0.08	38	1.80	496	<1	120	569	10	0.48	5	<5	<10	218	2776	<2	110	<10	18	36
205925	1369117	<0.005	<1	6.27	7	810	2	<1	0.48	5	22	160	34	4.23	0.06	36	1.67	481	<1	109	583	11	0.48	<5	<5	<10	283	2709	5	104	<10	18	30
205926D	1369117	<0.005	<1	6.30	10	797	2	<1	0.49	5	22	158	33	4.17	0.06	36	1.65	474	<1	109	568	9	0.49	<5	18	<10	280	2613	8	102	<10	18	27
205927	1369118	<0.005	<1	5.97	13	690	2	<1	0.49	5	23	166	51	4.13	0.28	34	1.60	529	<1	130	556	13	0.49	<5	6	<10	300	2484	9	93	<10	16	43
205928	1369119	<0.005	<1	5.93	12	604	2	<1	0.64	5	23	153	46	3.85	0.25	32	1.54	507	<1	112	536	16	0.52	<5	<5	<10	302	2441	<2	89	<10	16	72
205929	1369120	0.013	<1	>10.00	15	484	2	2	3.00	5	17	60	24	3.49	0.25	30	1.67	691	<1	51	652	14	0.76	<5	8	<10	350	3336	11	122	30	23	52
205930	1369121	0.006	<1	9.15	16	769	2	<1	0.87	5	23	169	45	4.24	0.14	43	1.72	518	<1	118	558	11	0.65	<5	12	<10	324	2832	3	107	<10	19	42
205931	1369122	<0.005	<1	>10.00	12	700	3	<1	1.08	5	27	166	46	4.43	0.23	53	1.88	560	<1	112	603	11	0.80	<5	15	<10	331	3180	4	115	<10	22	41
205932	1369123	0.006	<1	>10.00	8	654	3	<1	1.52	6	28	183	47	4.67	0.22	53	1.95	772	4	145	653	32	0.89	<5	13	<10	341	3481	8	121	<10	23	103
205933	1369124	<0.005	<1	>10.00	14	560	3	<1	1.23	6	26	168	45	4.34	0.18	43	1.76	674	<1	120	573	24	0.92	<5	18	<10	300	3055	7	111	<10	20	78

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/20/2012
 Date Completed: 08/08/2012
 Job #: 201242759
 Reference: TL12262
 Sample #: 321

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
205934	1369125	0.014	<1	6.56	16	551	2	<1	1.39	5	24	175	49	4.14	0.06	33	1.54	624	2	119	565	26	0.55	5	17	<10	358	2885	2	97	<10	17	77
205935	1369126	0.005	<1	8.96	14	550	2	4	1.66	5	25	178	45	4.03	0.12	40	1.56	647	5	129	555	20	0.70	<5	8	<10	384	3171	11	95	<10	19	68
205936	1369127	<0.005	<1	6.96	7	700	2	<1	1.14	6	27	185	48	4.43	0.10	29	1.62	673	2	132	572	29	0.56	<5	<5	<10	314	3279	2	109	<10	17	80
205937D	1369127	0.007	<1	8.23	12	683	2	<1	1.24	6	26	178	47	4.30	0.12	33	1.65	647	2	123	562	27	0.67	6	<5	<10	316	3208	8	105	<10	18	80
205938	1369128	<0.005	<1	7.32	12	654	2	<1	1.11	5	23	181	45	4.25	0.15	32	1.59	629	2	129	565	27	0.58	<5	11	<10	362	2980	6	99	<10	16	66
205939	1369129	0.005	<1	7.93	13	689	2	4	1.22	5	26	178	49	4.18	0.08	34	1.56	628	2	118	568	29	0.65	5	8	<10	370	3156	7	99	<10	17	84
205940	1369130	0.007	<1	6.64	9	583	2	<1	1.06	5	25	170	48	4.24	0.21	38	1.58	568	<1	114	577	23	0.52	<5	7	<10	321	3109	4	102	<10	16	82
205941	1369131	<0.005	<1	7.84	12	596	2	<1	1.34	4	21	173	42	3.67	0.29	40	1.52	501	3	118	519	27	0.70	<5	8	<10	405	2835	4	84	<10	16	57
205942	1369132	0.006	<1	8.01	11	650	2	<1	1.09	5	21	160	36	3.60	0.31	37	1.56	451	4	121	513	25	0.68	<5	13	<10	370	2652	10	81	<10	15	57
205943	1369133	0.005	<1	9.28	14	612	2	<1	1.21	5	26	188	41	4.39	0.28	45	1.71	546	7	155	540	24	0.68	<5	8	<10	294	3230	4	111	<10	19	67
205944	1369134	0.006	<1	7.94	12	517	2	<1	1.60	5	23	170	43	3.91	0.28	38	1.48	604	3	118	535	21	0.65	<5	6	<10	353	2982	<2	94	<10	18	60
205945	1369135	0.007	<1	8.47	14	589	3	<1	1.33	5	23	153	37	3.83	0.22	42	1.54	497	2	110	518	27	0.76	<5	6	<10	335	3101	3	100	<10	15	64
205946	1369136	0.006	2	8.04	16	613	2	<1	1.41	5	20	159	32	3.51	0.08	35	1.42	450	10	160	532	16	0.60	<5	9	<10	385	2721	5	81	<10	17	46
205947	1369137	0.006	<1	8.13	10	916	2	<1	1.66	4	13	77	17	2.59	0.15	27	1.15	338	<1	85	596	21	0.55	<5	7	<10	466	2511	4	56	<10	17	54
205948D	1369137	<0.005	<1	8.49	13	907	2	<1	1.68	<4	12	79	17	2.56	0.15	28	1.15	333	<1	89	584	16	0.59	<5	<5	11	464	2470	<2	55	<10	17	52
205949	1369138	<0.005	<1	7.06	13	612	2	<1	1.67	4	17	143	26	3.22	0.16	27	1.16	439	9	158	554	19	0.54	<5	15	<10	475	2564	3	67	<10	16	56
205950	1369139	<0.005	<1	7.28	8	701	2	<1	1.51	5	22	173	39	3.99	0.31	34	1.54	534	4	142	602	23	0.59	<5	11	<10	403	3072	3	94	<10	17	65
205951	1369140	0.256	<1	1.72	425	>5000	<2	<1	0.95	4	6	19	32	2.88	0.22	8	0.30	<100	7	19	<100	24	0.86	17	11	<10	138	890	6	16	53	10	27
205952	1369141	<0.005	<1	9.60	12	619	2	<1	1.59	6	26	183	40	4.38	0.28	44	1.74	558	8	169	605	23	0.71	5	16	<10	347	3452	6	110	<10	20	67
205953	1369142	<0.005	<1	7.76	14	564	2	<1	1.30	5	24	162	45	4.02	0.27	33	1.56	528	<1	101	559	25	0.64	<5	6	<10	332	3214	3	98	<10	18	63

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012

Final Certificate

Treasury Metals Inc
Exchange Tower 130 King St Suite 3680
Toronto, On, CAN
M5X 1B1
Ph#: (416) 599-4133
Fax#: (416) 599-4959
Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/20/2012
Date Completed: 08/08/2012
Job #: 201242759
Reference: TL12262
Sample #: 321

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
205954	1369143	<0.005	<1	5.60	9	613	2	<1	1.15	5	24	183	47	4.18	0.20	32	1.48	528	4	135	554	18	0.55	<5	9	<10	315	2858	6	92	<10	16	62
205955	1369144	<0.005	<1	8.42	11	607	2	<1	1.39	6	25	195	48	4.41	0.27	39	1.60	575	8	153	562	20	0.72	<5	17	<10	291	3352	4	107	<10	19	66
205956	1369145	<0.005	<1	5.71	14	607	2	<1	1.29	5	23	187	43	4.07	0.22	27	1.50	546	7	158	566	22	0.57	<5	12	<10	378	2942	3	91	<10	16	76
205957	1369146	0.005	<1	3.15	9	540	2	<1	0.94	5	22	168	43	3.92	0.12	21	1.41	514	<1	126	532	25	0.46	<5	7	<10	315	2546	2	84	<10	14	73
205958	1369147	<0.005	<1	6.30	7	614	2	<1	1.14	5	26	185	47	4.40	<0.01	31	1.62	570	<1	125	564	29	0.60	5	5	<10	349	3041	5	100	<10	17	71
205959R	1369147	<0.005	<1	7.28	12	617	2	2	1.25	5	27	175	46	4.24	0.17	33	1.60	563	<1	111	553	33	0.64	<5	<5	<10	364	3247	<2	100	<10	17	69
205960	1369148	<0.005	<1	9.79	13	683	2	<1	1.77	5	24	157	43	4.21	0.28	41	1.68	599	<1	109	726	27	0.80	<5	12	<10	427	3477	<2	105	<10	20	69
205961	1369149	<0.005	<1	6.80	15	745	2	4	1.80	5	21	138	39	3.62	0.21	26	1.40	513	3	114	858	27	0.65	<5	<5	<10	584	3074	5	82	<10	18	61
205962	1369150	<0.005	<1	8.06	11	684	3	<1	1.43	5	22	158	50	3.72	0.26	35	1.49	540	<1	85	556	32	0.69	<5	9	<10	408	3132	5	90	<10	18	64
205963	1369151	<0.005	<1	>10.00	10	663	2	<1	1.62	5	25	156	45	3.92	0.20	46	1.63	559	<1	91	570	21	0.84	<5	5	<10	344	3324	5	98	<10	20	60
205964	1369152	<0.005	<1	5.94	8	573	2	<1	1.84	5	24	157	44	4.06	0.18	29	1.60	587	<1	100	814	32	0.69	<5	6	<10	460	3158	6	92	<10	18	45
205965	1369153	<0.005	<1	7.04	12	653	2	<1	1.29	5	23	160	46	3.94	0.22	36	1.46	538	<1	97	535	23	0.65	<5	10	<10	337	3124	6	95	<10	17	67
205966	1369154	<0.005	<1	6.47	8	668	2	<1	1.33	5	23	157	45	3.79	0.16	31	1.39	529	<1	98	582	22	0.67	<5	8	<10	333	2981	<2	87	<10	16	57
205967	1369155	<0.005	<1	6.39	11	596	2	<1	1.17	5	21	148	37	3.37	0.26	27	1.35	464	<1	85	502	20	0.67	<5	11	<10	384	2797	7	78	<10	15	60
205968	1369156	<0.005	<1	4.87	5	621	2	<1	0.90	4	21	164	42	3.53	0.15	28	1.36	474	4	125	495	23	0.59	<5	9	<10	328	2574	<2	74	<10	14	67
205969	1369157	<0.005	<1	5.54	11	502	2	<1	1.22	4	21	147	40	3.18	0.22	22	1.22	415	<1	90	494	14	0.69	<5	12	<10	315	2644	4	75	<10	15	37
205970D	1369157	<0.005	<1	6.63	11	534	2	<1	1.37	5	21	155	42	3.31	0.16	26	1.29	428	<1	101	518	20	0.76	<5	7	<10	339	2818	6	80	<10	16	38
205971	1369158	<0.005	<1	7.41	8	710	2	<1	1.35	5	24	177	50	4.00	0.12	37	1.45	545	1	115	588	23	0.72	<5	<5	<10	343	3231	2	94	<10	18	74
205972	1369159	<0.005	<1	7.44	7	653	2	<1	1.45	5	23	153	43	3.58	0.15	37	1.37	514	<1	94	543	24	0.68	<5	7	<10	345	2951	5	83	<10	16	58
205973	1369160	0.242	<1	<0.01	440	>5000	<2	2	0.80	4	8	17	32	3.03	0.08	<1	0.22	<100	5	20	<100	25	0.66	16	13	<10	113	687	8	16	50	8	26

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
Jason Moore, General Manager

The results included on this report relate only to the items tested.
The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012

Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/20/2012
 Date Completed: 08/08/2012
 Job #: 201242759
 Reference: TL12262
 Sample #: 321

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
205974	1369161	<0.005	<1	7.03	8	639	2	<1	1.29	5	21	151	41	3.58	0.14	37	1.40	496	<1	97	537	23	0.64	<5	12	<10	332	2875	8	82	<10	16	67
205975	1369162	<0.005	<1	7.63	10	626	2	<1	1.39	4	21	137	39	3.54	0.23	37	1.42	467	<1	82	558	19	0.62	<5	7	<10	412	3021	<2	85	10	16	56
205976	1369163	0.006	<1	7.74	6	640	2	<1	1.27	4	21	139	38	3.45	0.14	36	1.43	469	<1	84	523	23	0.69	<5	6	<10	349	2872	3	80	<10	16	46
205977	1369164	<0.005	<1	7.99	14	621	2	<1	1.35	5	22	148	40	3.61	0.26	42	1.45	489	<1	91	537	25	0.69	<5	9	<10	366	2992	6	85	<10	17	59
205978	1369165	0.006	<1	8.73	10	613	2	<1	1.62	4	19	126	38	3.30	0.16	40	1.43	463	<1	71	567	20	0.76	<5	16	<10	415	2966	5	78	<10	17	62
205979	1369166	0.005	<1	4.17	11	609	2	<1	1.20	4	18	129	37	3.43	0.04	28	1.34	485	<1	84	577	25	0.46	<5	<5	<10	363	2765	3	75	<10	14	73
205980	1369167	0.008	<1	5.88	11	669	2	<1	1.35	4	22	159	43	3.55	0.29	27	1.28	554	<1	80	517	32	0.69	5	15	<10	377	2861	<2	79	<10	16	58
205981D	1369167	<0.005	<1	4.80	10	650	2	<1	1.22	4	21	160	43	3.58	0.23	24	1.24	553	<1	89	513	27	0.63	<5	<5	<10	356	2746	<2	77	<10	15	55
205982	1369168	0.006	<1	6.66	12	407	2	<1	1.45	8	26	158	46	6.28	0.05	28	1.28	565	<1	87	561	35	3.77	<5	<5	<10	409	2985	<2	81	<10	17	76
205983	1369169	<0.005	<1	7.96	10	675	3	<1	1.88	5	21	156	41	3.67	0.02	32	1.37	569	<1	86	604	27	1.05	6	8	10	464	3077	2	80	29	18	55
205984	1369170	<0.005	<1	7.23	9	664	2	<1	1.49	5	20	155	38	3.53	0.10	32	1.30	531	<1	96	511	24	0.80	6	9	<10	400	2837	2	76	<10	16	49
205985	1369171	<0.005	<1	8.42	11	653	2	<1	1.31	4	21	143	37	3.27	0.22	36	1.36	460	<1	81	473	27	0.85	5	6	<10	366	2731	5	73	<10	17	61
205986	1369172	<0.005	<1	8.89	13	661	2	<1	1.48	4	17	114	30	2.91	0.16	32	1.33	424	<1	79	532	28	0.77	5	<5	<10	426	2687	4	67	<10	17	84
205987	1369173	<0.005	<1	8.06	11	595	2	<1	1.40	5	21	150	38	3.39	0.14	35	1.33	490	<1	75	460	25	0.93	<5	<5	<10	350	2777	4	74	<10	17	66
205988	1369174	0.008	<1	6.32	12	720	<2	2	1.50	5	24	169	43	3.90	0.11	27	1.34	572	<1	78	480	26	0.99	5	10	<10	347	2918	2	83	<10	17	79
205989	1369175	0.016	<1	6.06	12	761	2	<1	1.37	4	22	149	40	3.63	0.15	23	1.25	556	<1	79	475	22	0.92	<5	8	<10	338	2867	2	79	<10	16	48
205990	1369176	<0.005	<1	5.81	9	658	2	<1	1.35	5	22	170	45	3.65	0.25	22	1.28	530	<1	80	471	21	0.87	<5	15	<10	314	2935	4	79	<10	16	79
205991	1369177	0.010	<1	5.97	18	618	3	<1	1.54	5	23	144	38	3.90	0.28	22	1.40	605	<1	80	601	22	0.86	5	7	<10	405	3168	4	90	<10	17	58
205992D	1369177	0.008	<1	3.96	11	591	2	<1	1.24	5	21	146	39	3.97	0.17	18	1.37	609	<1	85	606	21	0.77	<5	15	<10	344	3017	5	86	<10	16	58
205993	1369178	<0.005	<1	6.83	10	825	3	<1	2.10	4	17	78	23	2.86	0.33	14	1.39	450	<1	78	918	22	1.50	<5	12	<10	612	2938	3	64	<10	18	62

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012

Final Certificate

Treasury Metals Inc
Exchange Tower 130 King St Suite 3680
Toronto, On, CAN
M5X 1B1
Ph#: (416) 599-4133
Fax#: (416) 599-4959
Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/20/2012
Date Completed: 08/08/2012
Job #: 201242759
Reference: TL12262
Sample #: 321

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
205994	1369179	<0.005	<1	9.07	13	992	3	<1	1.68	<4	11	36	17	2.56	0.05	15	0.89	334	<1	56	1356	36	2.09	<5	13	<10	848	2455	5	41	<10	27	62
205995	1369180	<0.005	<1	7.65	12	466	2	4	2.70	5	18	60	24	3.56	0.15	19	1.56	702	<1	38	645	9	0.52	<5	12	<10	327	3272	<2	124	28	19	56
205996	1369181	<0.005	<1	>10.00	16	479	3	<1	1.90	9	25	82	100	6.28	0.30	36	1.40	339	<1	87	713	32	4.76	7	11	<10	534	1994	<2	51	10	22	352
205997	1369182	<0.005	<1	>10.00	17	557	3	4	2.07	5	19	105	32	3.79	0.28	36	1.67	450	<1	80	656	19	2.24	6	10	<10	418	2741	<2	79	<10	19	86
205998	1369183	0.005	<1	9.65	15	539	2	8	1.47	6	30	176	45	4.64	0.14	33	1.81	708	<1	101	579	27	0.76	<5	7	<10	261	3658	5	126	<10	20	78
205999	1369184	<0.005	<1	4.44	22	438	2	<1	0.86	6	27	162	48	4.37	<0.01	19	1.58	577	<1	94	560	25	0.41	5	6	<10	195	2805	4	105	<10	14	94
206000	1369185	<0.005	<1	>10.00	19	450	2	<1	1.59	6	26	166	51	4.53	0.09	37	1.78	637	<1	96	553	27	1.28	<5	9	<10	291	3049	<2	103	<10	17	76
206001	1369186	<0.005	<1	>10.00	15	505	2	<1	1.67	6	27	170	49	4.65	0.08	44	1.90	625	<1	95	567	24	1.38	<5	9	<10	288	3252	9	111	10	18	74
206002	1369187	<0.005	<1	>10.00	17	423	2	<1	1.66	6	29	169	56	4.42	0.12	39	1.84	592	<1	109	619	24	1.56	<5	8	<10	305	2831	7	108	<10	19	72
206003D	1369187	<0.005	<1	7.52	12	371	2	<1	1.25	6	26	161	52	4.30	0.34	25	1.70	563	<1	101	575	24	1.26	<5	15	<10	269	2480	5	103	<10	16	72
206004	1369188	0.005	<1	>10.00	14	596	3	<1	1.94	5	25	160	37	4.29	0.29	40	1.96	660	<1	100	827	24	0.75	5	5	<10	395	3751	5	109	<10	21	66
206005	1369189	<0.005	<1	9.99	23	606	3	<1	1.42	6	28	170	46	4.49	0.34	38	1.80	593	<1	104	608	20	0.76	<5	11	<10	290	3466	2	116	<10	17	60
206006	1369190	0.006	<1	>10.00	12	584	2	2	1.18	6	30	195	48	4.95	0.24	40	1.92	630	<1	138	578	25	0.86	<5	14	<10	225	3674	7	128	<10	15	54
206007	1369191	0.006	<1	8.88	13	471	2	3	1.35	7	29	133	68	5.36	0.32	27	1.44	507	<1	111	470	27	2.87	<5	7	<10	272	1826	<2	89	<10	14	214
206008	1369192	<0.005	<1	>10.00	14	530	2	<1	1.31	5	24	159	48	4.32	0.17	39	1.53	552	<1	114	524	37	1.85	<5	5	<10	288	2255	<2	96	11	16	110
206009	1369193	0.007	<1	8.47	19	467	2	<1	1.16	5	27	188	39	4.68	0.30	33	1.76	604	<1	129	542	25	0.62	<5	<5	<10	235	2932	4	122	<10	16	68
206010	1369194	0.012	<1	9.12	12	501	2	5	1.23	6	29	184	48	4.78	0.27	35	1.84	631	<1	126	497	26	0.73	<5	13	<10	205	3501	3	126	<10	16	44
206011	1369195	0.008	<1	9.95	6	501	3	2	0.75	7	30	195	44	5.41	0.11	42	2.25	500	<1	136	570	33	0.73	<5	11	<10	208	3947	4	154	<10	17	19
206012	1369196	0.006	<1	8.97	14	569	2	<1	1.00	6	30	191	52	4.96	0.05	33	1.91	636	<1	141	622	31	0.71	<5	7	<10	212	3810	7	134	<10	18	27
206013	1369197	0.008	<1	9.05	12	535	2	<1	0.98	6	31	197	50	5.24	0.16	38	2.09	581	<1	145	598	24	0.76	6	5	<10	221	3898	12	142	<10	18	34

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
Jason Moore, General Manager

The results included on this report relate only to the items tested.
The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/20/2012
 Date Completed: 08/08/2012
 Job #: 201242759
 Reference: TL12262
 Sample #: 321

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
206014D	1369197	0.008	<1	8.02	11	528	2	<1	0.92	7	31	201	52	5.23	0.25	33	2.03	571	1	158	599	29	0.69	<5	9	<10	218	3792	6	142	<10	17	32
206015	1369198	0.013	<1	8.17	12	494	2	<1	0.79	6	31	199	50	5.26	0.18	32	2.13	547	1	152	611	23	0.68	<5	11	<10	209	3593	<2	141	12	16	21
206016	1369199	0.011	<1	7.78	19	552	2	<1	1.47	6	26	162	48	4.84	0.21	29	2.00	590	<1	126	902	23	1.04	5	10	<10	352	3223	<2	124	<10	16	65
206017	1369200	1.862	<1	6.31	17	483	<2	2	2.53	5	21	60	33	4.01	0.28	15	1.59	756	<1	41	675	18	0.42	<5	6	<10	308	3177	5	133	29	18	62
206018	1369201	0.014	<1	9.91	16	642	3	2	0.76	7	32	175	48	5.14	0.27	38	2.09	589	<1	116	656	21	1.11	<5	7	<10	268	3427	5	142	10	18	66
206019	1369202	0.011	<1	6.88	35	632	2	<1	0.53	7	31	199	42	5.52	0.26	23	1.94	646	1	133	577	21	0.46	<5	9	<10	242	3711	6	150	<10	15	47
206020	1369203	0.010	<1	7.96	14	844	2	2	2.79	4	18	70	21	3.28	0.22	14	1.43	539	5	90	1468	23	0.87	<5	6	<10	1130	3725	6	76	<10	20	49
206021	1369204	0.019	<1	7.19	32	654	2	2	0.60	6	32	195	46	5.11	0.26	22	1.76	554	4	140	599	23	1.33	5	9	<10	248	3298	8	135	12	16	77
206022	1369205	0.010	<1	8.53	21	626	2	<1	1.05	6	29	163	34	5.01	0.29	23	1.90	592	3	122	949	28	0.64	5	<5	<10	281	3818	6	131	<10	20	73
206023	1369206	0.005	<1	7.41	32	622	3	<1	1.00	6	30	157	35	5.18	0.15	23	2.01	615	1	117	966	19	0.52	<5	14	<10	296	3780	4	135	<10	20	62
206024	1369207	0.006	<1	8.48	36	550	2	<1	0.99	7	31	204	47	5.42	0.15	24	1.96	657	3	135	612	26	0.65	<5	<5	<10	265	3875	6	151	<10	17	28
206025R	1369207	0.009	<1	6.91	32	531	2	<1	0.77	7	31	197	45	5.46	0.15	21	2.00	613	<1	124	580	25	0.51	6	7	<10	246	3708	7	151	<10	14	25
206026	1369208	0.009	<1	9.52	24	674	2	<1	1.22	6	28	191	46	4.56	0.11	25	1.55	566	7	122	616	22	0.87	<5	8	<10	271	3334	2	117	<10	17	58
206027	1369209	0.007	<1	7.06	10	672	2	<1	1.31	6	30	182	51	4.67	0.15	16	1.39	570	7	146	686	27	1.26	<5	16	<10	264	2958	5	107	11	15	93
206028	1369210	0.006	<1	9.96	11	643	2	<1	1.12	6	29	186	46	4.62	0.17	26	1.58	602	5	107	580	24	0.89	<5	16	<10	240	3553	2	120	<10	18	54
206029	1369211	0.018	<1	8.09	19	544	2	<1	0.70	7	33	205	52	5.62	0.22	27	2.00	612	2	136	587	27	0.58	<5	<5	<10	202	3726	3	151	<10	18	29
206030	1369212	0.005	<1	8.61	27	573	2	5	0.92	7	35	206	49	5.64	0.26	26	2.00	627	<1	128	608	27	0.68	<5	7	<10	178	3606	<2	152	<10	19	70
206031	1369213	<0.005	<1	7.64	18	630	2	<1	1.05	6	30	182	51	4.90	0.21	27	1.64	638	1	114	542	28	0.80	7	6	<10	207	3552	5	125	<10	18	74
206032	1369214	0.007	<1	8.33	27	488	2	3	1.46	6	27	184	42	4.58	0.18	30	1.53	831	5	110	513	15	0.80	<5	13	<10	156	3541	7	122	<10	17	55
206033	1369215	<0.005	<1	8.69	37	505	2	<1	1.01	6	29	197	46	4.70	0.30	32	1.77	753	4	126	555	18	1.67	<5	13	<10	132	3559	4	143	10	20	89

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012

Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/20/2012
 Date Completed: 08/08/2012
 Job #: 201242759
 Reference: TL12262
 Sample #: 321

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
206034	1369216	<0.005	<1	5.61	36	319	2	2	2.42	10	45	151	112	7.40	0.41	8	1.59	931	6	111	383	33	5.66	<5	6	10	223	2539	4	117	14	17	389
206035	1369217	<0.005	<1	4.34	20	290	<2	<1	2.62	8	37	140	114	6.13	0.17	4	1.50	869	2	100	298	34	4.39	<5	12	<10	149	2530	8	116	10	13	383
206036D	1369217	<0.005	<1	4.57	14	278	<2	4	2.71	9	39	139	116	6.29	0.38	5	1.54	891	3	102	304	24	4.56	<5	<5	<10	152	2589	<2	119	13	13	393
206037	1369218	<0.005	<1	5.94	23	335	2	<1	1.99	8	29	46	62	4.72	0.12	17	1.04	562	<1	78	380	30	3.60	<5	6	<10	200	1884	3	56	18	10	842
206038	1369219	0.006	<1	6.70	17	384	2	5	1.68	7	26	126	90	5.38	0.15	13	1.04	529	3	128	470	30	4.12	<5	9	<10	241	2737	<2	100	14	16	448
206039	1369220	5.147	74	4.88	51	572	<2	<1	1.43	25	18	50	57	3.65	0.13	5	0.84	548	2	34	623	702	0.80	63	5	277	258	2353	<2	105	69	15	2022
206040	1369221	<0.005	<1	5.55	11	454	<2	<1	2.07	<4	4	50	18	1.25	0.33	<1	0.51	530	4	77	271	15	0.94	<5	8	<10	295	895	<2	19	<10	5	177
206041	1369222	<0.005	<1	7.02	9	586	<2	<1	2.34	<4	3	35	6	0.93	0.28	3	0.40	376	2	42	254	18	0.85	<5	<5	<10	309	877	<2	17	<10	5	62
206042	1369223	<0.005	<1	6.97	13	670	<2	<1	2.55	<4	4	40	3	0.96	0.26	4	0.44	562	4	50	234	19	0.70	5	9	<10	319	937	5	17	10	6	37
206043	1369224	<0.005	<1	7.21	9	627	<2	<1	1.90	<4	7	42	5	1.95	0.41	11	0.75	627	2	51	443	21	0.76	<5	14	<10	259	1890	3	28	10	12	91
206044	1369225	<0.005	<1	5.94	10	732	<2	<1	1.51	<4	4	40	3	1.52	0.43	11	0.62	453	3	54	264	17	0.65	<5	12	<10	183	1080	<2	12	<10	8	103
206045	1369226	<0.005	<1	6.50	13	770	<2	<1	1.61	<4	4	55	4	1.72	0.45	12	0.68	524	7	84	263	18	0.70	<5	8	<10	192	1045	<2	15	<10	8	92
206046	1369227	<0.005	<1	6.69	12	954	<2	<1	1.65	<4	5	33	7	1.45	0.40	13	0.72	424	2	40	276	19	0.70	<5	7	<10	206	1242	8	17	<10	8	64
206047D	1369227	<0.005	<1	6.57	17	975	<2	<1	1.67	<4	6	50	7	1.59	0.25	12	0.72	429	6	75	283	18	0.69	<5	10	<10	212	1221	<2	19	<10	8	67
206048	1369228	<0.005	<1	4.48	10	637	<2	<1	1.28	<4	5	34	29	1.53	0.11	10	0.71	301	2	58	308	20	0.58	<5	<5	<10	190	1173	<2	17	<10	7	83
206049	1369229	0.006	<1	5.97	12	1034	<2	<1	0.73	<4	4	41	24	1.22	0.14	16	0.59	198	7	69	241	19	0.49	<5	12	<10	171	1060	3	13	<10	8	56
206050	1369230	<0.005	<1	7.25	16	836	2	<1	1.17	<4	3	36	18	1.12	0.14	23	0.80	207	5	47	242	11	0.66	<5	12	<10	162	1084	<2	12	<10	9	34
206051	1369231	<0.005	<1	4.15	7	1050	2	<1	0.78	<4	6	42	31	1.72	0.14	14	0.66	414	4	76	254	14	0.79	<5	14	<10	149	1007	<2	14	<10	7	56
206052	1369232	0.012	<1	5.93	11	1104	2	8	0.66	4	5	49	43	1.73	0.13	16	0.51	440	7	78	238	10	0.72	<5	10	<10	156	1032	11	12	<10	8	186
206053	1369233	0.013	<1	5.40	8	1194	<2	<1	0.66	<4	4	32	32	1.37	0.32	15	0.51	361	<1	41	229	12	0.60	<5	12	<10	176	1007	6	11	<10	7	115

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012

Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/20/2012
 Date Completed: 08/08/2012
 Job #: 201242759
 Reference: TL12262
 Sample #: 321

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
206054	1369234	0.021	<1	5.81	11	1204	<2	<1	0.70	<4	5	40	56	1.58	0.34	21	0.62	527	5	58	229	17	0.66	<5	9	<10	180	1055	2	13	<10	8	90
206055	1369235	0.044	<1	5.87	11	1070	<2	<1	1.02	<4	5	40	12	1.27	0.35	15	0.61	374	3	61	263	11	0.52	<5	8	<10	208	1144	<2	16	<10	7	43
206056	1369236	0.013	<1	5.89	12	1136	<2	<1	0.69	<4	4	40	10	1.27	0.33	20	0.55	382	4	66	256	20	0.59	<5	6	<10	197	1051	<2	12	<10	8	215
206057	1369237	<0.005	<1	5.31	8	1730	<2	<1	0.68	<4	5	61	13	1.48	0.29	21	0.66	326	8	108	217	16	0.51	<5	10	<10	237	1033	<2	13	10	7	38
206058D	1369237	0.040	<1	2.98	11	1537	<2	<1	0.43	<4	5	56	13	1.46	0.25	16	0.66	325	6	108	209	14	0.37	<5	11	<10	198	936	<2	12	<10	6	44
206059	1369238	0.059	<1	5.08	10	1309	<2	<1	0.70	<4	4	24	5	1.13	0.22	21	0.71	331	<1	36	222	12	0.40	<5	6	<10	239	1016	4	11	<10	7	36
206060	1369239	0.019	<1	6.32	10	1431	<2	<1	0.86	<4	5	36	7	1.21	0.22	19	0.66	305	2	55	226	12	0.52	<5	12	<10	249	1071	2	12	<10	8	35
206061	1369240	IS																															
206062	1369241	<0.005	<1	5.78	13	954	<2	<1	0.80	<4	4	49	11	1.35	0.19	19	0.64	309	6	78	243	13	0.42	<5	7	<10	198	1058	2	13	<10	8	33
206063	1369242	<0.005	<1	8.10	15	754	2	<1	1.11	<4	4	43	11	1.37	0.28	23	0.68	302	6	56	260	14	0.61	<5	5	<10	164	1161	3	15	<10	10	30
206064	1369243	0.005	<1	1.77	12	345	<2	<1	0.40	<4	4	17	23	1.38	0.10	8	0.51	232	<1	32	142	10	0.62	<5	8	<10	96	718	<2	9	<10	5	58
206065	1369244	<0.005	<1	6.24	9	661	2	<1	1.27	<4	4	30	51	1.36	0.24	18	0.72	289	1	45	252	16	0.55	<5	11	<10	168	1097	<2	13	<10	8	48
206066	1369245	<0.005	<1	4.80	8	654	<2	2	1.22	<4	6	36	34	1.50	0.35	16	0.87	271	1	60	267	5	0.48	<5	8	<10	113	1069	3	14	<10	8	37
206067	1369246	<0.005	<1	6.12	14	681	<2	<1	1.37	<4	6	43	49	1.65	0.28	19	0.89	281	4	66	263	10	0.66	<5	6	<10	119	1131	<2	16	<10	9	42
206068	1369247	0.016	<1	6.72	12	696	<2	<1	1.45	<4	3	51	7	1.37	0.34	22	0.95	265	6	79	247	12	0.49	6	10	<10	92	1050	<2	14	<10	9	36
206069D	1369247	<0.005	<1	3.73	9	604	<2	<1	1.25	<4	3	43	6	1.37	0.14	16	0.97	268	2	81	229	13	0.24	<5	9	<10	86	887	5	11	<10	7	36
206070	1369248	<0.005	<1	4.52	7	684	<2	<1	1.32	<4	5	41	27	1.37	0.19	18	1.13	328	4	73	234	8	0.30	<5	12	<10	92	917	2	11	<10	7	43
206071	1369249	<0.005	<1	2.82	9	528	<2	<1	1.76	<4	6	24	7	1.46	0.18	19	1.36	382	<1	48	332	18	0.17	<5	<5	<10	116	992	8	18	<10	5	45
206072	1369250	<0.005	<1	7.92	15	729	<2	<1	2.08	<4	9	79	10	2.03	0.32	25	1.25	389	10	101	375	10	0.81	<5	7	<10	115	1578	4	37	<10	10	31
206073	1369251	<0.005	<1	5.02	10	580	<2	3	1.60	<4	10	58	15	2.02	0.20	20	1.16	337	2	68	366	11	0.55	<5	13	<10	115	1414	5	35	<10	8	36

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/20/2012
 Date Completed: 08/08/2012
 Job #: 201242759
 Reference: TL12262
 Sample #: 321

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
206074	1369252	0.007	<1	7.94	17	618	<2	<1	1.50	<4	5	44	8	1.46	0.23	23	0.82	272	7	56	272	8	0.79	8	<5	<10	124	1246	6	17	<10	8	34
206075	1369253	<0.005	<1	3.54	12	397	<2	<1	1.29	<4	12	92	4	2.47	0.12	27	1.05	361	4	110	383	12	0.39	<5	<5	<10	140	1527	3	44	<10	10	49
206076	1369254	<0.005	<1	5.56	7	671	2	<1	1.40	<4	8	44	27	1.90	0.81	25	0.71	335	2	69	329	31	0.43	<5	10	<10	307	1574	3	31	<10	7	52
206077	1369255	0.072	1	<0.01	16	85	3	17	0.51	35	23	63	81	26.77	0.05	1	1.38	5905	6	148	154	74	>10.00	<5	5	<10	60	562	19	18	15	6	272
206078	1369256	0.138	10	2.00	18	117	4	15	1.55	35	20	71	69	27.02	0.58	5	1.65	7633	13	118	140	119	>10.00	<5	6	<10	67	715	9	23	<10	10	325
206079	1369257	0.047	12	2.20	12	90	2	10	5.63	11	13	48	17	8.38	0.63	24	3.19	3013	11	69	766	217	5.18	<5	9	<10	679	1600	9	43	14	12	205
206080D	1369257	0.063	8	1.18	13	120	2	4	5.53	11	14	58	18	8.46	0.43	22	3.17	3011	11	95	776	214	5.09	<5	10	<10	674	1560	5	44	14	11	206
206081	1369258	0.006	<1	2.95	14	1688	2	<1	2.33	11	16	69	22	9.08	0.93	52	2.05	3011	6	104	1181	48	1.36	6	5	<10	986	2279	5	55	56	13	85
206082	1369259	0.012	<1	0.28	9	812	2	11	0.91	20	9	68	11	15.81	0.03	<1	2.56	7980	12	109	<100	27	3.48	<5	5	<10	76	231	13	9	26	7	105
206083	1369260	0.227	<1	<0.01	439	>5000	<2	<1	0.71	4	8	27	32	2.96	<0.01	<1	0.05	<100	11	19	<100	23	0.75	14	9	<10	102	891	6	16	59	8	58
206084	1369261	0.005	<1	<0.01	11	559	2	6	3.57	16	5	48	6	12.75	<0.01	<1	2.81	6715	4	71	<100	27	2.03	<5	<5	<10	169	248	13	11	11	7	96
206085	1369262	<0.005	<1	<0.01	10	185	2	8	1.90	17	5	68	6	13.72	<0.01	<1	2.27	7320	7	98	<100	30	2.21	<5	8	<10	112	258	13	16	14	9	101
206086	1369263	0.006	<1	<0.01	6	84	<2	2	1.58	13	3	71	6	11.03	0.82	<1	1.91	4688	8	126	<100	25	1.98	6	6	<10	116	217	4	16	37	7	90
206087	1369264	0.008	<1	<0.01	8	43	2	7	1.51	21	5	53	7	16.74	<0.01	<1	2.38	5334	7	91	<100	29	2.75	<5	<5	<10	62	160	6	15	15	7	106
206088	1369265	0.014	<1	1.25	11	106	2	12	1.12	23	7	74	10	18.43	0.27	<1	2.88	8812	15	121	<100	33	3.79	<5	<5	<10	41	273	19	16	14	9	116
206089	1369266	0.011	<1	1.42	14	158	3	14	1.41	24	7	60	11	18.54	0.31	<1	2.92	7979	11	95	<100	39	4.29	<5	11	<10	52	283	9	15	20	10	117
206090	1369267	<0.005	<1	<0.01	9	65	<2	<1	0.50	8	3	85	6	6.75	<0.01	<1	1.26	3525	12	126	<100	19	1.81	<5	<5	<10	21	174	5	8	<10	5	45
206091R	1369267	0.006	<1	0.48	12	91	<2	<1	0.41	7	3	95	5	5.51	0.09	<1	0.96	2529	15	132	<100	15	1.68	<5	8	<10	22	221	<2	9	<10	6	39
206092	1369268	0.008	<1	0.29	10	356	<2	5	2.66	17	4	59	8	13.01	0.03	<1	2.88	7569	8	88	<100	17	3.26	<5	5	<10	57	222	<2	10	<10	8	74
206093	1369269	0.008	<1	1.03	11	88	<2	<1	2.15	10	2	50	7	7.67	0.21	<1	1.75	3663	5	61	<100	16	2.42	<5	6	<10	44	248	7	9	<10	8	41

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/20/2012
 Date Completed: 08/08/2012
 Job #: 201242759
 Reference: TL12262
 Sample #: 321

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
206094	1369270	0.007	<1	<0.01	11	21	<2	8	1.14	18	5	69	8	14.40	<0.01	<1	2.30	6274	10	121	<100	25	2.88	<5	16	<10	24	148	8	12	13	6	89
206095	1369271	0.024	<1	<0.01	12	192	<2	9	2.90	16	8	65	10	12.61	<0.01	<1	2.59	4491	9	97	138	37	6.09	<5	12	<10	129	456	10	17	30	9	122
206096	1369272	0.080	2	<0.01	14	25	4	21	1.14	47	66	46	81	36.57	0.08	2	1.34	2482	7	267	<100	104	>10.00	<5	9	<10	39	400	11	13	10	7	152
206097	1369273	0.040	5	2.02	11	79	4	26	2.00	42	31	194	68	32.46	0.15	18	2.42	9240	<1	248	257	78	>10.00	<5	8	<10	75	1491	5	58	<10	13	205
206098	1369274	0.015	<1	5.01	8	159	2	<1	4.42	15	35	398	15	12.02	0.46	55	3.18	3913	<1	241	497	21	3.25	5	7	<10	178	2982	6	113	<10	16	99
206099	1369275	0.012	<1	4.54	12	230	2	4	4.67	15	34	340	17	12.28	0.41	61	3.14	4119	<1	229	529	14	3.49	<5	10	<10	171	2942	5	103	<10	17	104
206100	1369276	0.013	<1	3.54	12	152	2	11	4.52	17	46	385	27	13.48	0.29	51	3.23	4441	<1	291	498	14	3.88	<5	9	<10	165	2771	5	103	<10	13	106
206101	1369277	0.006	<1	4.44	10	270	<2	<1	3.99	9	36	400	25	7.09	0.30	49	2.85	2721	<1	262	533	15	1.02	<5	7	<10	159	3196	5	109	<10	12	78
206102D	1369277	0.007	<1	4.69	7	275	<2	4	3.99	9	34	403	25	7.09	0.36	50	2.84	2691	<1	264	530	13	1.04	<5	5	<10	159	3032	<2	108	<10	12	80
206103	1369278	0.007	<1	4.69	15	462	2	9	3.77	10	38	415	37	8.39	0.38	68	3.76	2791	<1	265	765	17	1.22	<5	8	<10	413	3082	17	112	<10	15	88
206104	1369279	0.009	<1	4.40	11	390	<2	1	3.88	9	39	449	36	6.69	0.31	72	3.54	2155	<1	268	710	13	0.70	<5	<5	<10	335	3054	10	109	<10	14	78
206105	1369280	0.006	<1	4.60	14	459	<2	<1	2.37	5	18	63	24	3.52	0.37	4	1.33	695	<1	37	642	12	0.34	6	13	<10	282	2999	<2	123	24	17	66
206106	1369281	0.006	<1	5.67	14	211	<2	6	4.98	11	39	465	28	8.51	0.47	53	3.29	3293	<1	259	516	12	1.11	<5	17	<10	228	3364	7	114	10	14	111
206107	1369282	0.009	<1	5.89	17	332	<2	<1	4.47	8	38	320	34	6.85	0.49	56	3.34	1556	<1	228	615	11	1.66	<5	<5	<10	281	3352	6	106	<10	13	71
206108	1369283	0.008	<1	4.61	12	195	<2	<1	3.73	5	36	281	34	4.77	0.39	46	3.08	966	<1	218	464	9	0.90	5	8	<10	191	2389	10	99	<10	11	54
206109	1369284	0.010	<1	5.20	5	143	<2	2	3.90	5	31	253	31	4.18	0.45	34	2.86	876	3	206	453	10	0.77	<5	5	<10	166	2058	4	96	<10	11	63
206110	1369285	0.011	<1	3.70	14	146	<2	<1	4.20	7	42	264	40	5.67	0.38	33	2.96	1189	<1	224	458	16	1.59	<5	9	<10	147	2280	8	93	11	10	114
206111	1369286	0.009	<1	4.80	17	181	<2	<1	4.22	7	43	259	37	5.63	0.43	37	3.00	1199	<1	215	470	16	1.64	<5	6	<10	152	2527	5	98	<10	11	121
206112	1369287	<0.005	<1	4.29	9	306	<2	<1	1.83	<4	7	36	7	1.70	0.33	39	1.20	382	<1	62	275	16	0.36	<5	<5	<10	121	1132	<2	19	<10	7	53
206113D	1369287	<0.005	<1	4.14	12	305	<2	<1	1.83	<4	7	35	6	1.70	0.32	39	1.20	380	<1	64	280	12	0.33	<5	9	<10	123	1152	<2	19	<10	6	54

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By:  Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012

Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/20/2012
 Date Completed: 08/08/2012
 Job #: 201242759
 Reference: TL12262
 Sample #: 321

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
206114	1369288	<0.005	<1	4.44	10	332	2	<1	2.69	<4	10	50	3	1.95	0.28	38	1.46	586	5	73	326	7	0.42	<5	<5	<10	125	1434	<2	27	<10	7	43
206115	1369289	<0.005	<1	4.05	10	355	<2	<1	1.66	<4	6	42	2	1.66	0.31	38	1.15	398	<1	63	265	11	0.34	6	12	<10	107	1174	<2	18	<10	6	58
206116	1369290	<0.005	<1	4.16	12	345	<2	<1	1.83	<4	7	33	5	1.84	0.51	38	1.35	375	<1	59	329	13	0.29	<5	14	<10	200	1326	<2	20	<10	7	64
206117	1369291	<0.005	<1	4.72	12	735	2	<1	2.37	<4	15	45	12	2.47	0.36	62	1.60	440	<1	72	708	15	0.34	7	14	<10	504	2506	2	50	10	10	70
206118	1369292	<0.005	<1	3.35	13	317	<2	2	2.82	<4	5	28	2	1.74	0.33	23	1.60	713	<1	49	240	14	0.25	<5	7	<10	121	1011	5	14	<10	6	83
206119	1369293	<0.005	<1	4.15	9	566	2	<1	2.27	<4	12	68	12	2.32	0.38	41	1.33	447	<1	75	673	18	0.35	<5	9	<10	525	2365	6	46	<10	9	73
206120	1369294	<0.005	<1	3.89	11	515	<2	<1	2.75	<4	9	54	9	2.27	0.39	36	1.46	627	<1	70	504	21	0.31	<5	9	<10	327	1754	2	39	<10	7	86
206121	1369295	0.009	<1	5.07	13	429	<2	<1	2.47	<4	12	61	18	2.41	0.42	43	1.32	505	<1	74	506	13	0.41	<5	12	<10	270	1758	3	47	<10	6	86
206122	1369296	0.006	<1	4.46	12	587	<2	<1	1.80	<4	13	63	8	2.28	0.32	51	1.16	329	<1	73	753	13	0.27	<5	12	<10	544	1630	2	48	<10	9	52
206123	1369297	0.007	<1	4.82	12	457	<2	<1	2.88	<4	14	79	19	2.28	0.30	39	1.10	436	<1	86	476	17	0.33	<5	7	<10	344	1874	<2	45	<10	6	65
206124D	1369297	<0.005	<1	6.62	10	519	<2	<1	3.21	<4	14	86	19	2.39	0.32	44	1.13	458	<1	88	490	14	0.43	<5	6	<10	380	2114	6	50	<10	7	65
206125	1369298	0.264	<1	6.04	6	547	<2	1	2.24	<4	8	35	4	1.75	0.25	30	0.60	283	1	54	453	11	0.30	<5	10	<10	333	1892	<2	36	<10	6	45
206126	1369299	0.005	<1	5.85	8	654	<2	<1	1.81	<4	7	28	6	1.60	0.31	29	0.58	230	<1	43	445	8	0.29	<5	<5	<10	382	1736	<2	33	<10	5	31
206127	1369300	1.819	<1	4.88	19	498	<2	<1	2.38	5	20	66	34	4.00	0.29	5	1.41	759	<1	38	680	14	0.34	<5	9	<10	287	3258	5	132	30	17	76
206128	1369301	0.034	<1	6.53	17	629	<2	<1	1.49	<4	8	30	17	1.50	0.29	27	0.52	210	<1	38	447	12	0.41	<5	13	<10	321	1777	2	32	<10	6	37
206129	1369302	0.006	<1	4.29	12	615	2	<1	3.60	4	12	46	11	2.52	0.41	28	1.73	659	<1	73	457	18	0.36	<5	6	<10	290	1698	5	39	<10	6	101
206130	1369303	<0.005	<1	4.28	11	650	2	<1	3.24	<4	9	38	10	2.18	0.45	33	1.84	757	<1	74	526	22	0.36	5	13	<10	455	1479	2	29	<10	10	125
206131	1369304	<0.005	<1	5.85	17	1779	2	<1	2.82	4	17	44	17	3.10	0.43	69	1.72	558	<1	72	1666	39	0.73	<5	11	<10	1543	3253	2	74	<10	21	66
206132	1369305	<0.005	<1	5.76	11	648	<2	<1	1.81	<4	7	29	3	1.76	0.45	41	1.39	416	<1	70	295	13	0.34	<5	12	<10	228	1217	3	17	<10	8	97
206133	1369306	0.005	<1	5.70	9	665	2	<1	1.84	<4	6	31	3	1.70	0.41	38	1.33	389	<1	63	279	17	0.32	<5	15	<10	226	1261	2	17	<10	8	90

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/20/2012
 Date Completed: 08/08/2012
 Job #: 201242759
 Reference: TL12262
 Sample #: 321

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
206134	1369307	<0.005	<1	4.76	8	542	<2	<1	5.20	6	38	356	16	5.01	0.37	38	3.59	998	<1	239	592	19	0.34	<5	7	<10	226	3453	3	108	<10	11	127
206135D	1369307	<0.005	<1	6.06	9	539	<2	<1	5.38	6	37	353	16	4.96	0.40	41	3.55	987	<1	232	578	13	0.43	5	6	<10	243	3616	10	111	<10	12	116
206136	1369308	0.007	<1	5.74	10	270	<2	<1	5.24	6	41	360	37	5.14	0.41	45	4.02	1047	<1	258	606	15	0.37	<5	7	<10	278	2976	4	119	11	12	97
206137	1369309	<0.005	<1	6.47	11	336	<2	<1	4.73	6	40	361	55	5.05	0.42	49	3.56	1051	<1	227	613	13	0.39	<5	6	<10	265	3705	<2	121	<10	13	105
206138	1369310	<0.005	<1	5.29	11	146	<2	<1	3.88	6	36	342	51	4.58	0.46	45	3.71	1029	<1	230	506	11	0.50	7	8	<10	224	2453	7	104	10	11	129
206139	1369311	<0.005	<1	4.98	11	215	<2	<1	3.82	6	40	394	39	4.90	0.52	67	4.07	827	<1	244	571	14	0.35	<5	9	<10	217	2975	8	116	<10	12	87
206140	1369312	0.007	<1	6.68	11	370	<2	<1	4.49	6	36	335	42	4.58	0.62	56	3.82	843	<1	221	688	18	0.44	<5	15	<10	345	3344	3	114	<10	13	95
206141	1369313	<0.005	<1	4.20	9	292	2	<1	3.51	6	41	390	22	5.06	0.48	86	4.17	881	<1	255	521	12	0.32	<5	9	<10	169	3083	8	109	<10	11	102
206142	1369314	<0.005	<1	4.52	11	188	2	<1	3.15	6	42	278	77	5.16	0.48	66	3.88	862	<1	210	726	12	0.73	<5	<5	<10	160	3693	2	107	10	12	85
206143	1369315	0.005	<1	4.19	6	270	<2	1	3.24	6	38	342	39	4.87	0.44	60	3.82	834	<1	240	606	10	0.48	<5	<5	<10	231	2763	2	103	<10	11	101
206144	1369316	0.005	<1	4.05	9	183	<2	<1	4.03	6	35	369	16	4.72	0.41	39	3.74	926	<1	236	555	12	0.28	<5	6	<10	228	2830	<2	109	<10	11	93
206145	1369317	0.005	<1	4.12	9	65	<2	<1	3.21	6	36	387	4	4.96	0.41	44	4.53	802	<1	255	547	9	0.26	<5	10	<10	166	2197	8	112	<10	11	86
206146D	1369317	0.009	<1	3.76	6	62	<2	<1	3.13	6	38	383	4	4.95	0.30	43	4.53	797	<1	254	554	12	0.25	<5	7	<10	159	2186	6	111	<10	11	88
206147	1369318	<0.005	<1	4.19	6	119	<2	<1	3.78	7	42	394	15	5.33	0.35	42	4.25	912	<1	253	589	8	0.31	<5	18	<10	197	2676	6	121	<10	11	93
206148	1369319	0.008	<1	4.75	9	260	<2	1	4.91	5	35	302	33	4.31	0.38	32	3.15	911	<1	219	557	9	0.28	6	6	<10	309	3474	4	109	<10	11	89
206149	1369320	<0.005	<1	3.96	10	414	<2	<1	2.36	4	17	55	23	3.50	0.47	6	1.44	691	<1	42	632	12	0.27	5	7	<10	294	2871	<2	121	23	16	60
206150	1369321	<0.005	<1	3.70	10	365	2	<1	4.25	5	31	262	46	3.88	0.43	31	3.20	794	<1	175	418	10	0.51	<5	8	<10	348	2726	8	84	23	9	93
206151	1369322	<0.005	<1	4.21	12	608	<2	<1	4.42	6	36	322	43	4.72	0.45	39	3.55	815	<1	197	663	13	0.32	<5	7	<10	474	3428	7	107	<10	12	110
206152	1369323	<0.005	<1	5.59	9	566	<2	<1	1.96	<4	9	40	15	1.91	0.47	33	1.10	279	<1	74	592	11	0.32	5	13	<10	510	1972	9	38	<10	7	41
206153	1369324	<0.005	<1	4.43	12	511	<2	<1	2.04	<4	17	83	10	2.74	0.37	32	1.23	438	<1	76	961	16	0.28	<5	8	<10	609	3413	2	64	25	12	55

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By:  Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012

Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/20/2012
 Date Completed: 08/08/2012
 Job #: 201242759
 Reference: TL12262
 Sample #: 321

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
206154	1369325	<0.005	<1	4.83	5	456	<2	<1	1.21	<4	8	29	5	1.69	0.37	22	0.69	295	<1	54	525	16	0.29	<5	<5	<10	350	1897	2	32	<10	7	47
206155	1369326	0.005	<1	4.28	10	422	<2	<1	1.10	<4	8	31	5	1.65	0.38	20	0.64	290	<1	63	455	12	0.28	<5	6	<10	304	1757	<2	30	<10	6	45
206156	1369327	<0.005	<1	4.64	8	381	<2	<1	1.06	<4	7	38	6	1.59	0.37	15	0.46	231	<1	73	405	6	0.28	<5	9	<10	248	1707	<2	28	<10	5	47
206157R	1369327	0.006	<1	4.26	9	373	<2	<1	0.97	<4	6	32	5	1.53	0.31	16	0.46	221	<1	57	407	11	0.29	<5	15	<10	226	1651	2	27	<10	5	43
206158	1369328	<0.005	<1	4.37	11	430	<2	<1	1.25	<4	6	33	8	1.53	0.34	16	0.53	281	<1	60	396	7	0.27	<5	11	<10	298	1696	<2	27	<10	5	51
206159	1369329	0.006	<1	4.05	12	1063	<2	<1	1.46	<4	6	36	1	1.55	0.45	15	0.66	267	<1	67	403	16	0.26	<5	5	<10	645	1596	3	27	<10	5	58
206160	1369330	0.020	<1	4.30	12	712	<2	<1	1.43	<4	7	41	4	1.71	0.46	18	0.80	316	<1	73	500	14	0.31	<5	9	<10	588	1725	8	30	<10	7	57
206161	1369331	0.005	<1	4.07	12	762	2	<1	1.50	<4	10	33	10	2.34	0.44	21	0.89	479	<1	59	949	18	0.37	<5	7	<10	852	2393	<2	46	<10	14	50
206162	1369332	0.006	<1	5.11	8	464	<2	<1	0.89	<4	6	43	7	1.82	0.41	12	0.49	334	<1	82	412	11	0.32	<5	16	<10	403	1737	<2	29	<10	6	38
206163	1369333	<0.005	<1	4.50	7	369	<2	<1	0.87	<4	6	34	5	1.67	0.37	13	0.62	342	<1	65	408	10	0.25	<5	10	<10	255	1586	<2	26	<10	5	45
206164	1369334	<0.005	<1	4.28	9	321	<2	<1	1.16	<4	5	31	<1	1.56	0.38	11	0.80	318	<1	60	396	6	0.24	<5	10	<10	200	1346	<2	25	<10	5	42
206165	1369335	<0.005	<1	4.85	10	342	<2	<1	1.33	<4	6	18	2	1.59	0.36	12	0.91	346	<1	37	410	15	0.26	<5	13	<10	187	1371	3	27	<10	5	44
206166	1369336	<0.005	<1	5.16	6	373	<2	<1	0.83	<4	6	31	17	1.74	0.34	10	0.68	316	<1	58	397	12	0.27	<5	6	<10	177	1560	2	28	<10	5	45
206167	1369337	<0.005	<1	5.70	9	422	<2	<1	1.06	<4	6	35	13	1.77	0.31	12	0.67	353	<1	60	407	11	0.28	<5	6	<10	250	1641	2	28	<10	6	37
206168D	1369337	<0.005	<1	5.00	9	407	<2	<1	0.98	<4	6	37	13	1.74	0.31	10	0.63	345	<1	67	400	9	0.25	<5	11	<10	238	1580	2	27	<10	5	32
206169	1369338	0.006	<1	4.91	13	462	<2	<1	1.45	<4	7	45	12	1.98	0.37	12	0.85	492	<1	80	409	11	0.28	<5	<5	<10	325	1520	5	29	<10	6	47
206170	1369339	0.018	<1	5.01	8	439	<2	<1	1.10	<4	7	49	6	2.06	0.31	13	0.72	420	1	91	417	12	0.27	<5	10	<10	289	1668	<2	29	<10	6	49
206171	1369340	5.130	62	3.45	53	465	<2	<1	1.28	23	15	34	52	3.20	0.28	6	0.90	503	<1	31	570	658	0.66	52	<5	252	248	1934	5	93	62	14	1903
206172	1369341	0.006	<1	5.00	8	367	<2	<1	1.30	<4	7	37	11	2.06	0.35	12	0.74	436	<1	71	390	13	0.28	<5	12	<10	266	1612	2	28	<10	6	49
206173	1369342	<0.005	<1	4.72	14	373	<2	<1	1.25	<4	6	36	1	1.71	0.36	12	0.75	400	<1	68	384	12	0.27	<5	10	<10	249	1640	<2	28	<10	5	47

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012

Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/20/2012
 Date Completed: 08/08/2012
 Job #: 201242759
 Reference: TL12262
 Sample #: 321

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
206174	1369343	0.010	<1	4.23	10	382	<2	<1	1.33	<4	7	41	2	1.59	0.38	9	0.67	319	<1	75	383	14	0.26	<5	<5	<10	265	1614	3	27	<10	5	40
206175	1369344	0.005	<1	5.66	14	849	2	<1	2.68	4	19	72	20	3.20	0.39	26	1.59	468	<1	121	1037	16	0.47	<5	7	<10	844	3470	<2	76	<10	13	58
206176	1369345	<0.005	<1	5.47	9	958	2	<1	2.49	4	18	77	18	3.26	0.32	27	1.61	481	<1	125	1054	15	0.47	<5	5	<10	760	3447	7	75	<10	13	63
206177	1369346	<0.005	<1	4.67	11	912	2	<1	2.19	4	16	62	14	3.01	0.32	24	1.53	448	<1	102	1040	17	0.38	5	5	<10	713	3322	4	70	<10	13	62
206178	1369347	<0.005	<1	4.62	13	425	<2	<1	1.60	<4	8	38	3	1.63	0.22	12	0.79	313	<1	70	384	12	0.33	<5	<5	<10	275	1701	<2	30	<10	5	41
206179D	1369347	<0.005	<1	4.83	10	443	<2	<1	1.65	<4	6	36	3	1.65	0.21	12	0.79	318	<1	67	398	14	0.33	<5	<5	<10	280	1734	3	30	<10	5	42
206180	1369348	<0.005	<1	5.49	4	441	<2	<1	1.55	<4	5	29	<1	1.51	0.36	14	0.80	236	<1	53	393	11	0.28	<5	11	<10	290	1631	5	28	<10	5	37
206181	1369349	<0.005	<1	4.57	8	449	<2	<1	1.46	<4	7	43	1	1.76	0.36	11	0.84	293	<1	76	442	9	0.24	<5	7	<10	278	1480	5	30	<10	5	45
206182	1369350	<0.005	<1	4.39	13	513	<2	<1	1.25	<4	5	27	1	1.48	0.39	11	0.83	254	<1	55	389	9	0.28	<5	11	<10	252	1458	4	27	<10	5	37
206183	1369351	<0.005	<1	4.50	10	440	<2	<1	1.21	<4	5	46	5	1.66	0.32	10	0.78	288	<1	88	403	13	0.24	<5	8	<10	217	1371	2	29	<10	5	41
206184	1369352	<0.005	<1	4.61	9	420	<2	<1	1.38	<4	6	34	1	1.57	0.31	10	0.90	272	<1	65	395	9	0.25	<5	13	<10	220	1384	3	28	<10	5	47
206185	1369353	<0.005	<1	4.35	5	416	<2	1	1.60	<4	5	52	2	1.71	0.31	10	0.96	314	3	102	377	6	0.26	<5	6	<10	219	1388	<2	28	<10	5	64
206186	1369354	<0.005	<1	3.92	9	389	<2	<1	1.20	<4	6	47	1	1.55	0.26	9	0.79	242	<1	86	376	12	0.22	<5	7	<10	196	1417	3	26	<10	4	43
206187	1369355	<0.005	<1	4.55	10	444	<2	<1	1.55	<4	7	39	5	1.70	0.33	15	0.97	325	<1	71	452	9	0.25	<5	12	<10	310	1704	3	30	<10	6	45
206188	1369356	<0.005	<1	5.71	14	1135	2	<1	2.53	4	18	66	4	3.33	0.27	26	1.47	546	2	113	1208	26	0.50	<5	13	<10	1058	3555	7	75	<10	18	58
206189	1369357	<0.005	<1	3.73	5	406	<2	<1	1.21	<4	6	36	3	1.46	0.27	11	0.79	277	<1	63	413	6	0.26	<5	<5	<10	248	1494	6	25	<10	5	35
206190D	1369357	0.006	<1	7.06	6	494	2	<1	1.62	<4	7	38	3	1.61	0.39	20	0.91	290	<1	67	420	11	0.40	5	<5	<10	320	1757	4	30	<10	7	38
206191	1369358	0.006	<1	5.43	8	400	<2	<1	1.33	<4	6	29	<1	1.47	0.38	14	0.74	254	<1	53	368	10	0.35	<5	9	<10	351	1526	<2	25	<10	5	35
206192	1369359	<0.005	<1	6.68	8	681	2	5	1.46	<4	5	36	2	1.44	0.36	17	0.61	197	<1	66	383	13	0.36	<5	<5	<10	643	1644	2	25	<10	7	36
206193	1369360	<0.005	<1	4.60	12	432	<2	<1	2.44	5	17	55	23	3.53	0.28	8	1.45	700	<1	35	633	10	0.30	<5	8	<10	308	3032	3	122	26	17	54

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012

Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/20/2012
 Date Completed: 08/08/2012
 Job #: 201242759
 Reference: TL12262
 Sample #: 321

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
206194	1369361	0.006	<1	5.50	5	479	2	<1	1.64	<4	6	34	2	1.53	0.37	16	0.82	256	<1	61	437	11	0.33	<5	5	<10	410	1593	<2	29	<10	6	32
206195	1369362	<0.005	<1	5.59	14	423	<2	<1	1.60	<4	6	47	4	1.57	0.24	13	0.72	208	2	90	379	13	0.29	<5	<5	<10	323	1415	<2	28	<10	5	93
206196	1369363	0.043	<1	5.49	10	479	<2	<1	1.50	<4	5	31	3	1.47	0.20	13	0.69	203	<1	57	367	13	0.26	<5	6	<10	372	1395	2	26	<10	5	55
206197	1369364	0.005	<1	6.37	9	426	<2	<1	1.85	<4	7	54	3	1.73	0.11	18	0.76	251	3	98	455	15	0.32	<5	11	<10	372	1412	<2	30	<10	6	54
206198	1369365	<0.005	<1	7.76	12	573	<2	<1	1.78	<4	8	38	5	1.80	0.14	25	0.89	266	<1	73	590	15	0.48	<5	7	<10	495	1731	4	36	<10	9	58
206199	1369366	0.007	<1	7.89	13	577	2	<1	2.06	<4	7	27	4	1.72	0.12	24	0.89	302	<1	54	555	16	0.48	6	11	<10	502	1727	2	35	<10	9	50
206200	1369367	0.006	<1	7.62	8	777	2	<1	1.62	<4	7	52	9	1.77	0.17	22	0.81	261	2	87	594	13	0.45	<5	6	<10	666	1861	<2	35	<10	10	52
206201D	1369367	0.005	<1	5.71	11	754	2	<1	1.42	<4	7	46	9	1.70	0.13	16	0.74	254	<1	78	582	14	0.34	<5	10	<10	618	1801	<2	34	<10	9	46
206202	1369368	<0.005	<1	7.51	17	1267	3	<1	2.59	4	15	69	14	3.09	0.27	38	1.40	565	3	104	1478	31	0.82	<5	<5	<10	1343	3075	6	72	<10	22	58
206203	1369369	<0.005	<1	7.72	15	1234	3	<1	2.66	<4	13	59	20	2.85	0.36	38	1.40	505	<1	81	1466	29	0.73	<5	7	<10	1306	3052	<2	72	<10	22	53
206204	1369370	0.011	<1	5.99	7	704	2	<1	1.02	<4	5	50	5	1.44	0.34	16	0.52	184	3	95	368	17	0.38	5	10	<10	511	1500	4	23	<10	7	39
206205	1369371	<0.005	<1	4.97	11	721	2	<1	0.95	<4	5	51	5	1.38	0.30	16	0.46	167	3	97	349	15	0.32	<5	<5	<10	532	1471	<2	21	<10	7	45
206206	1369372	<0.005	<1	6.16	15	757	2	<1	1.01	<4	5	56	6	1.41	0.34	19	0.46	158	5	108	353	14	0.39	<5	5	<10	586	1452	<2	22	<10	8	42
206207	1369373	<0.005	<1	2.79	9	864	2	<1	0.66	<4	5	51	6	1.34	0.05	11	0.33	138	2	92	353	20	0.24	<5	5	<10	507	1507	<2	19	<10	7	44
206208	1369374	<0.005	<1	3.66	8	782	<2	<1	0.85	<4	5	55	8	1.43	0.10	13	0.39	163	5	103	358	20	0.22	<5	9	<10	527	1517	3	21	<10	6	44
206209	1369375	0.006	<1	4.79	11	869	2	<1	0.87	<4	4	47	6	1.31	0.09	15	0.34	134	2	88	345	18	0.29	<5	9	<10	667	1476	5	20	<10	7	42
206210	1369376	0.006	<1	4.92	9	607	2	<1	1.10	<4	5	73	6	1.68	0.16	17	0.56	220	9	137	363	14	0.29	<5	<5	<10	459	1472	3	26	<10	6	43
206211	1369377	<0.005	<1	5.62	9	439	2	<1	1.24	<4	5	41	<1	1.51	0.08	18	0.65	221	1	74	384	15	0.31	<5	7	<10	361	1354	<2	28	<10	5	39
206212D	1369377	<0.005	<1	5.45	9	434	<2	<1	1.22	<4	5	42	1	1.51	0.12	17	0.64	221	1	77	381	11	0.29	<5	11	<10	356	1320	2	28	<10	5	39
206213	1369378	<0.005	<1	4.97	8	588	<2	<1	1.13	<4	5	37	4	1.38	0.24	18	0.55	201	<1	69	365	15	0.29	5	<5	<10	492	1425	2	23	<10	6	46

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012

Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/20/2012
 Date Completed: 08/08/2012
 Job #: 201242759
 Reference: TL12262
 Sample #: 321

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
206214	1369379	<0.005	<1	4.46	12	386	<2	<1	1.34	<4	5	43	1	1.52	0.26	12	0.60	219	<1	80	366	10	0.25	<5	17	<10	374	1338	<2	26	<10	5	41
206215	1369380	0.240	<1	<0.01	423	>5000	<2	<1	0.75	4	5	16	30	2.86	0.18	1	0.21	<100	4	20	<100	19	0.69	14	11	<10	113	751	2	14	52	8	20
206216	1369381	0.005	<1	5.12	10	396	2	<1	1.58	<4	5	40	6	1.43	0.21	12	0.59	204	<1	71	358	12	0.34	<5	5	<10	388	1115	2	25	<10	5	33
206217	1369382	<0.005	<1	5.27	8	284	<2	<1	1.50	<4	5	39	1	1.51	0.26	12	0.63	215	<1	72	371	11	0.29	<5	6	<10	281	1030	5	26	<10	5	39
206218	1369383	<0.005	<1	5.11	13	268	<2	<1	1.66	<4	4	41	2	1.54	0.21	9	0.57	223	<1	74	367	12	0.26	<5	9	<10	283	971	<2	26	<10	5	38
206219	1369384	<0.005	<1	4.04	12	302	<2	<1	1.43	<4	5	71	3	1.73	0.17	9	0.53	231	9	135	351	11	0.24	<5	10	<10	236	965	2	28	<10	5	40
206220	1369385	<0.005	<1	4.33	10	294	<2	<1	1.15	<4	5	47	2	1.56	0.13	13	0.70	212	1	93	376	10	0.23	<5	6	<10	241	1232	2	28	<10	5	43
206221	1369386	<0.005	<1	5.67	10	303	<2	<1	1.36	<4	6	56	2	1.60	0.21	16	0.74	213	4	103	375	12	0.29	<5	<5	<10	278	1267	7	29	<10	5	37
206222	1369387	<0.005	<1	5.54	7	283	2	<1	1.58	<4	5	30	<1	1.36	0.15	14	0.66	170	<1	55	366	14	0.31	<5	10	<10	344	1432	3	27	<10	5	34
206223R	1369387	<0.005	<1	5.46	12	286	2	<1	1.58	<4	6	45	1	1.50	0.25	13	0.66	181	<1	85	366	12	0.30	5	6	<10	344	1427	5	29	<10	5	36
206224	1369388	<0.005	<1	4.85	11	247	<2	<1	1.53	<4	6	29	18	1.45	0.24	13	0.66	204	<1	53	370	12	0.48	<5	7	<10	382	1324	<2	26	<10	5	30
206225	1369389	<0.005	<1	4.44	6	235	<2	<1	1.15	<4	7	40	12	1.60	0.28	14	0.70	239	<1	75	385	11	0.26	<5	9	<10	201	1247	<2	27	<10	5	40
206226	1369390	<0.005	<1	4.01	9	225	2	<1	1.13	<4	6	33	2	1.40	0.21	11	0.63	210	<1	64	359	11	0.25	<5	6	<10	216	1318	2	27	<10	5	35
206227	1369391	<0.005	<1	4.74	10	250	<2	<1	1.46	<4	6	36	1	1.56	0.21	13	0.59	241	<1	66	376	9	0.26	<5	8	<10	245	1452	<2	26	<10	5	42
206228	1369392	<0.005	<1	4.15	12	237	<2	11	1.22	<4	6	42	3	1.45	0.22	13	0.66	248	<1	76	377	11	0.25	<5	<5	<10	250	1180	<2	26	<10	5	40
206229	1369393	<0.005	<1	4.78	9	565	<2	<1	1.72	<4	7	39	17	1.68	0.21	18	0.74	246	<1	76	529	21	0.44	<5	9	<10	721	1347	<2	31	<10	7	41
206230	1369394	<0.005	<1	4.54	9	253	<2	<1	1.39	<4	6	52	7	1.55	0.26	13	0.54	223	3	94	373	11	0.28	<5	13	<10	345	1403	<2	26	<10	5	35
206231	1369395	<0.005	<1	5.55	8	244	<2	<1	1.31	<4	6	45	10	1.47	0.21	17	0.63	221	1	78	336	13	0.34	<5	7	<10	296	1289	<2	25	<10	5	33
206232	1369396	<0.005	<1	5.12	9	306	<2	<1	1.27	<4	6	51	7	1.73	0.19	12	0.62	246	2	97	378	12	0.28	<5	9	<10	261	1349	9	28	<10	5	41
206233	1369397	<0.005	<1	5.50	11	391	<2	<1	1.82	<4	7	48	2	1.74	0.30	15	0.61	247	3	89	379	11	0.29	<5	14	<10	282	1202	2	29	<10	6	29

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/20/2012
 Date Completed: 08/08/2012
 Job #: 201242759
 Reference: TL12262
 Sample #: 321

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
206234D	1369397	0.006	<1	5.51	9	382	<2	<1	1.76	<4	5	54	2	1.71	0.31	15	0.59	240	4	97	367	11	0.30	<5	8	<10	277	1184	<2	28	<10	6	28
206235	1369398	<0.005	<1	5.48	8	405	<2	<1	1.48	<4	5	22	2	1.28	0.31	17	0.63	198	<1	46	292	14	0.30	6	10	<10	299	896	8	21	<10	6	23
206236	1369399	<0.005	<1	5.06	9	512	<2	<1	1.52	<4	5	21	1	1.22	0.20	19	0.63	203	<1	43	278	10	0.28	<5	9	<10	375	927	3	20	<10	6	21
206237	1369400	<0.005	<1	4.74	19	418	<2	<1	2.40	4	17	54	23	3.47	0.23	9	1.45	689	<1	36	625	9	0.33	<5	11	<10	301	2951	<2	119	23	17	55
206238	1369401	<0.005	<1	5.20	8	254	<2	<1	1.69	<4	5	18	<1	1.21	0.20	15	0.56	177	<1	34	292	8	0.29	<5	5	<10	292	844	9	19	<10	6	14
206239	1369402	<0.005	<1	5.60	9	347	<2	<1	1.72	<4	3	14	<1	1.10	0.27	12	0.53	139	<1	30	278	6	0.28	<5	10	<10	337	825	<2	19	<10	6	12
206240	1369403	0.005	<1	5.50	7	349	<2	<1	2.31	<4	3	19	<1	1.19	0.26	17	0.67	180	<1	41	278	10	0.29	<5	7	<10	324	709	4	19	<10	6	14
206241	1369404	<0.005	<1	3.94	10	349	<2	<1	1.92	<4	5	19	1	1.30	0.22	13	0.68	204	<1	36	309	7	0.24	<5	12	<10	252	852	<2	23	<10	6	14
206242	1369405	0.014	<1	3.56	12	253	<2	<1	4.28	6	45	289	64	5.02	0.22	24	1.78	1080	<1	117	1425	8	0.32	<5	5	<10	270	6952	<2	164	<10	18	92
206243	1369406	0.012	<1	7.95	15	299	<2	<1	5.50	6	50	331	69	5.47	0.31	26	1.80	1201	1	123	1685	12	0.56	<5	13	<10	374	8565	8	189	<10	21	99
206244	1369407	0.016	<1	8.39	15	278	<2	2	5.10	7	65	352	55	5.62	0.36	25	1.82	1190	<1	223	1706	7	0.54	<5	7	<10	315	8761	11	205	<10	22	174
206245D	1369407	0.007	<1	7.86	11	272	<2	<1	5.11	7	66	353	56	5.66	0.44	25	1.86	1164	<1	226	1721	6	0.47	<5	6	<10	316	8259	3	205	<10	22	180
206246	1369408	0.006	<1	5.85	9	228	<2	<1	4.50	6	47	250	49	4.39	0.48	11	1.42	1057	<1	126	1529	7	0.43	<5	8	<10	254	7798	<2	169	<10	19	92

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, July 30, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/26/2012
 Date Completed: 07/13/2012
 Job #: 201242328
 Reference: TL 12 263
 Sample #: 69

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
178740	1360844	0.013	<1	5.78	20	534	<2	20	1.32	<4	10	29	13	2.13	<0.01	21	0.96	608	<1	25	527	17	1.11	<5	11	10	167	2211	9	45	<10	7	62
178741	1360845	0.016	<1	5.38	16	468	<2	41	0.96	<4	7	17	3	0.62	<0.01	15	0.52	116	<1	23	333	11	0.62	<5	15	13	199	1395	16	27	<10	4	15
178742	1360846	0.007	<1	5.76	18	516	<2	21	1.05	<4	8	18	3	0.65	<0.01	15	0.53	137	<1	26	359	12	0.68	<5	10	10	201	1278	<2	26	<10	5	18
178743	1360847	0.008	<1	4.19	15	450	<2	5	0.94	<4	6	14	4	0.68	0.07	11	0.49	143	<1	18	317	10	0.73	<5	8	<10	178	1111	4	23	<10	4	17
178744	1360848	0.013	<1	5.09	12	483	<2	12	1.46	<4	4	15	6	0.67	<0.01	12	0.51	199	<1	18	355	13	0.67	<5	8	<10	208	1217	7	25	14	4	21
178745	1360849	0.010	<1	6.68	7	598	<2	9	1.78	<4	5	24	11	0.86	<0.01	17	0.62	239	<1	22	394	14	0.74	<5	15	14	254	1538	7	30	<10	6	21
178746	1360850	<0.005	<1	3.57	12	364	<2	22	2.17	<4	15	52	21	3.29	<0.01	8	1.35	648	<1	28	568	5	0.31	<5	6	<10	250	2748	13	111	15	15	50
178747	1360851	0.007	<1	6.49	11	586	<2	17	1.35	<4	5	16	4	0.77	<0.01	18	0.66	214	<1	16	378	13	0.68	<5	10	<10	225	1564	8	28	<10	5	23
178748	1360852	0.006	<1	4.21	13	505	<2	8	1.22	<4	4	19	9	0.75	<0.01	13	0.57	227	<1	20	353	16	0.51	<5	8	<10	184	1509	10	27	<10	4	31
178749	1360853	0.035	<1	6.30	11	581	<2	26	1.91	<4	9	16	12	1.95	0.11	18	0.91	538	<1	21	488	75	1.18	<5	10	<10	208	1940	12	38	<10	6	273
178750D	1360853	0.071	<1	6.93	18	568	<2	<1	1.93	<4	9	17	11	1.83	<0.01	19	0.90	506	<1	17	464	69	1.17	<5	<5	11	211	1887	9	36	<10	7	252
178751	1360854	0.176	<1	6.42	21	566	<2	<1	1.60	<4	10	61	14	1.48	<0.01	20	1.18	512	<1	40	597	46	1.05	<5	5	<10	161	2156	6	39	<10	7	98
178752	1360855	0.045	3	5.00	18	466	<2	15	0.80	<4	4	18	5	0.88	<0.01	14	0.66	582	<1	18	365	594	0.83	<5	9	11	129	1431	9	27	<10	5	342
178753	1360856	0.081	4	4.71	18	433	<2	28	0.72	<4	3	14	6	0.85	0.24	13	0.62	426	<1	18	321	877	0.84	5	11	10	123	1342	7	25	10	4	641
178754	1360857	0.052	<1	4.73	16	338	<2	20	1.27	<4	4	17	3	0.70	<0.01	10	0.57	480	<1	18	373	44	0.72	<5	12	<10	144	1216	11	24	<10	5	107
178755	1360858	0.243	2	5.96	25	387	<2	23	0.68	<4	6	13	28	0.71	0.05	14	0.58	239	<1	19	325	40	0.95	<5	12	<10	163	1431	4	24	<10	5	30
178756	1360859	0.052	<1	5.71	23	385	<2	12	1.02	<4	11	13	6	0.59	<0.01	17	0.70	416	<1	23	322	24	0.59	<5	5	<10	124	1380	15	25	<10	5	92
178757	1360860	0.265	<1	0.06	418	>5000	<2	20	0.84	<4	7	19	29	2.81	<0.01	3	0.24	<100	9	11	<100	17	0.69	16	9	12	111	757	16	15	39	8	19
178758	1360861	0.020	<1	6.85	23	529	<2	4	1.27	<4	7	12	2	0.70	0.74	18	0.71	423	<1	19	342	26	0.74	<5	14	10	135	1521	8	28	<10	5	65
178759	1360862	0.013	<1	5.64	16	462	<2	31	0.71	<4	5	12	2	0.59	<0.01	15	0.76	384	<1	14	375	23	0.58	<5	11	<10	111	1631	10	26	<10	4	33

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By:  Derek Demianuk H.Bsc., Laboratory Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Monday, July 30, 2012

Final Certificate

Treasury Metals Inc
Exchange Tower 130 King St Suite 3680
Toronto, On, CAN
M5X 1B1
Ph#: (416) 599-4133
Fax#: (416) 599-4959
Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 06/26/2012
Date Completed: 07/13/2012
Job #: 201242328
Reference: TL 12 263
Sample #: 69

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
178760	1360863	0.020	<1	6.01	27	307	<2	40	1.49	<4	4	12	1	0.82	0.60	14	0.62	362	<1	14	360	21	0.90	<5	11	<10	123	1363	12	27	<10	5	25
178761D	1360863	0.018	<1	4.32	28	284	<2	26	1.29	<4	3	10	12	0.81	0.13	9	0.56	365	<1	14	354	26	0.82	<5	10	10	108	1290	7	26	<10	4	105
178762	1360864	0.032	<1	5.92	48	345	<2	10	0.85	<4	6	14	7	1.28	0.16	14	0.62	354	<1	15	359	23	1.44	<5	12	12	102	1551	11	26	<10	5	128
178763	1360865	0.056	2	6.19	23	355	<2	21	1.48	<4	5	13	16	1.17	0.32	15	1.02	688	<1	14	345	61	1.05	<5	7	<10	124	1586	7	27	<10	5	215
178764	1360866	0.028	1	8.49	18	304	<2	6	2.21	<4	6	19	8	1.35	0.04	24	1.31	915	<1	19	373	26	1.16	<5	14	10	165	1701	18	28	<10	7	48
178765	1360867	0.061	<1	8.60	22	373	<2	16	1.60	<4	6	15	3	1.09	0.06	28	1.04	614	<1	17	324	23	1.13	<5	16	<10	141	1724	16	26	<10	7	48
178766	1360868	0.808	4	9.22	40	424	2	17	0.84	<4	5	15	8	1.35	0.16	27	0.72	276	<1	19	338	141	1.66	7	7	12	113	1745	8	27	10	8	516
178767	1360869	0.035	1	>10.00	33	538	2	23	2.16	<4	6	17	5	1.56	<0.01	32	1.10	598	<1	23	361	18	1.30	<5	13	<10	145	1913	10	30	<10	7	41
178768	1360870	<0.005	<1	7.80	16	489	<2	30	2.65	<4	16	57	21	3.28	<0.01	30	1.34	660	<1	37	540	11	0.80	<5	10	14	300	3299	15	115	20	13	56
178769	1360871	0.270	2	9.40	31	411	<2	<1	2.78	<4	6	17	5	1.72	0.04	33	0.87	520	<1	23	349	15	1.52	<5	12	<10	249	1656	8	30	<10	7	50
178770	1360872	0.013	2	9.56	55	415	<2	40	1.68	<4	9	14	4	1.62	0.19	33	0.65	291	<1	29	342	15	2.02	<5	10	14	221	1660	2	28	<10	7	66
178771	1360873	<0.005	1	6.52	39	410	<2	13	2.25	<4	17	12	3	1.26	0.07	16	0.53	382	<1	37	355	23	1.49	<5	12	<10	240	1424	14	27	<10	5	180
178772D	1360873	0.007	1	6.36	43	368	<2	12	2.14	<4	17	12	3	1.24	0.10	17	0.53	362	<1	32	345	21	1.48	<5	12	11	221	1360	8	26	<10	5	174
178773	1360874	<0.005	1	8.04	40	434	<2	22	2.40	<4	12	18	2	1.22	0.34	19	0.53	302	<1	32	364	21	1.62	<5	10	<10	272	1561	7	29	<10	6	66
178774	1360875	0.011	<1	5.53	30	353	<2	9	1.54	<4	12	13	<1	0.91	0.05	11	0.51	229	<1	26	357	15	1.15	<5	10	12	209	1347	13	26	<10	5	37
178775	1360876	0.011	<1	5.33	35	365	<2	19	1.37	<4	10	14	<1	0.91	0.05	10	0.48	203	<1	24	358	17	1.14	5	11	<10	202	1374	6	26	<10	5	35
178776	1360877	0.007	1	7.75	28	322	<2	24	2.09	<4	9	53	9	0.98	0.06	22	0.71	271	2	54	253	15	1.11	<5	9	10	265	1172	5	25	<10	6	19
178777	1360878	0.013	1	7.60	23	574	<2	27	0.83	<4	7	25	3	1.70	0.08	19	0.49	163	<1	36	359	18	2.03	5	8	<10	230	1428	8	28	<10	6	27
178778	1360879	0.007	1	7.88	35	675	<2	15	0.74	<4	8	28	15	1.67	0.05	27	0.63	193	<1	33	377	18	2.02	<5	9	<10	221	1729	3	36	<10	6	36
178779	1360880	2.060	1	7.67	16	502	<2	28	2.59	4	17	58	30	3.83	0.11	27	1.46	711	<1	34	584	13	0.69	<5	10	<10	301	3348	14	126	21	15	60

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By:  Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.
The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
The results generated by this procedure are not accredited at this time and therefore are informational only.

Monday, July 30, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 06/26/2012
 Date Completed: 07/13/2012
 Job #: 201242328
 Reference: TL 12 263
 Sample #: 69

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
178780	1360881	0.022	3	>10.00	14	856	2	22	1.90	4	28	151	45	4.05	<0.01	47	1.28	401	3	97	550	25	2.64	<5	6	12	326	3016	6	110	<10	13	118
178781	1360882	0.012	1	9.84	28	461	2	28	2.09	<4	9	29	9	1.75	<0.01	29	1.24	680	<1	37	495	49	1.44	<5	9	15	147	1877	14	42	<10	8	80
178782	1360883	0.060	1	9.98	35	507	2	24	0.56	<4	7	27	7	1.49	0.50	24	0.54	<100	2	36	481	54	1.92	<5	10	12	107	1711	<2	40	<10	8	69
178783D	1360883	0.050	1	6.16	29	419	<2	19	0.15	<4	8	24	7	1.53	0.04	7	0.37	<100	<1	34	505	52	1.73	5	13	10	77	1389	4	35	<10	7	73
178784	1360884	0.492	5	5.13	33	402	<2	42	0.36	<4	6	24	36	1.52	0.03	9	0.51	165	<1	36	451	59	1.70	5	12	13	72	1232	7	31	<10	6	154
178785	1360885	0.108	<1	7.18	41	590	2	21	1.15	<4	7	25	16	1.51	<0.01	12	0.88	512	<1	35	500	59	1.20	<5	14	10	97	1659	10	40	<10	7	87
178786	1360886	0.149	1	7.47	59	577	2	<1	1.02	<4	10	28	15	1.68	0.37	13	0.81	433	<1	40	504	58	1.45	<5	12	<10	88	1860	5	41	11	7	292
178787	1360887	0.537	3	6.36	52	495	<2	10	0.42	<4	8	27	17	1.68	0.32	10	0.51	177	<1	39	469	65	1.75	<5	7	<10	74	1675	5	38	<10	6	242
178788	1360888	0.377	2	6.97	48	489	2	46	0.90	<4	8	29	19	1.45	0.24	18	0.60	221	<1	39	421	73	1.56	<5	10	10	97	1712	8	38	<10	6	85
178789	1360889	0.136	3	8.43	50	630	2	22	1.56	<4	9	30	16	1.87	0.15	26	1.01	581	1	41	486	150	1.79	<5	7	12	116	2059	6	43	11	6	120
178790	1360890	0.006	<1	7.44	18	490	<2	31	2.84	4	17	62	23	3.65	0.17	26	1.48	725	<1	32	609	10	0.64	<5	16	15	325	3495	14	127	24	15	53
178791	1360891	0.335	4	7.06	49	654	2	19	0.58	<4	8	28	42	1.47	0.14	28	0.54	117	3	35	426	66	1.76	6	13	<10	90	2124	2	41	10	6	168
178792	1360892	0.480	5	8.38	33	652	2	34	0.66	<4	7	27	21	1.05	0.20	26	0.58	118	1	38	446	47	1.24	<5	15	10	91	2161	8	40	12	7	85
178793	1360893	0.232	1	>10.00	42	725	2	30	1.18	<4	9	29	23	1.40	0.18	32	0.83	261	3	37	494	52	1.49	<5	10	11	118	2396	13	44	12	9	100
178794D	1360893	0.256	2	>10.00	45	717	2	19	1.14	<4	10	29	24	1.40	0.02	31	0.79	258	3	42	499	54	1.48	5	14	12	117	2319	6	43	10	8	104
178795	1360894	0.306	1	5.84	37	517	<2	32	0.13	<4	6	22	40	1.08	<0.01	8	0.41	<100	<1	37	412	43	1.11	<5	9	<10	57	1763	5	34	10	6	99
178796	1360895	0.118	1	5.14	41	531	<2	34	0.83	<4	8	21	20	1.39	<0.01	9	0.66	301	<1	33	425	59	1.15	<5	12	<10	81	1733	6	33	<10	6	127
178797	1360896	0.117	1	8.86	37	625	2	13	1.16	<4	8	25	22	1.49	0.18	20	0.85	340	<1	32	470	76	1.35	<5	11	<10	103	2067	6	38	10	8	113
178798	1360897	0.013	<1	6.24	20	634	2	14	1.80	<4	9	191	15	1.70	0.13	15	1.02	513	<1	99	499	48	0.59	<5	8	11	108	2206	6	41	<10	6	80
178799	1360898	0.025	<1	4.51	12	643	<2	<1	1.85	<4	8	23	2	1.60	0.37	11	0.97	404	<1	31	455	32	0.49	<5	13	12	106	2150	14	40	<10	5	84

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By:  Derek Demianuk H.Bsc., Laboratory Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Monday, July 30, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 06/26/2012
 Date Completed: 07/13/2012
 Job #: 201242328
 Reference: TL 12 263
 Sample #: 69

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
178800	1360899	0.016	<1	7.17	15	602	2	23	2.30	<4	8	28	4	1.69	0.23	24	1.15	496	<1	27	455	27	0.75	<5	12	<10	132	2233	4	39	<10	6	75
178801	1360900	5.088	63	5.95	46	509	<2	16	1.61	21	14	38	49	3.28	0.35	22	0.95	488	2	25	495	550	0.88	69	11	220	248	2216	2	93	54	12	1717
178802	1360901	0.070	2	7.21	21	713	2	2	2.14	<4	9	25	5	1.86	0.20	26	1.10	429	<1	32	465	49	1.13	<5	14	12	126	2285	17	43	11	6	88
178803	1360902	0.168	5	6.73	52	542	2	31	0.81	<4	7	36	45	1.66	0.17	25	0.62	168	2	38	382	509	1.91	<5	11	11	101	1884	3	38	11	6	345
178804	1360903	0.166	3	8.77	43	725	2	14	1.18	8	9	40	109	2.12	<0.01	31	0.83	287	3	42	427	364	2.42	6	11	11	116	2176	3	44	29	7	1950
178805R	1360903	0.185	3	>10.00	40	722	2	7	1.19	8	9	38	99	2.18	<0.01	31	0.89	279	2	38	444	358	2.58	<5	17	<10	116	2142	14	43	27	9	1895
178806	1360904	0.014	1	>10.00	18	787	3	14	2.73	<4	10	32	13	2.01	<0.01	38	1.33	491	3	37	504	58	1.20	<5	10	15	141	2415	12	45	<10	8	114
178807	1360905	0.168	1	6.38	17	451	2	14	0.91	6	7	27	79	1.44	0.17	19	0.75	280	<1	34	433	59	1.19	<5	13	<10	92	1949	10	36	19	6	1132
178808	1360906	0.076	<1	5.39	6	467	<2	7	0.89	<4	8	21	10	1.14	0.25	16	0.72	235	<1	30	456	22	0.70	5	11	<10	94	1919	5	36	<10	5	58
178809	1360907	0.017	<1	6.02	12	370	<2	27	1.14	<4	5	18	22	1.15	0.31	15	0.84	264	<1	27	266	34	0.68	<5	12	<10	102	1296	2	22	<10	5	178
178810	1360908	0.320	5	6.12	46	313	<2	25	0.62	16	4	22	44	1.45	0.28	13	0.69	254	2	32	200	1279	1.81	<5	12	<10	67	1098	8	19	47	5	4254
178811	1360909	0.053	<1	5.24	28	288	<2	36	0.91	<4	4	34	20	1.53	0.27	13	1.10	393	2	43	235	45	1.49	<5	11	<10	71	1057	12	19	<10	4	180
178812	1360910	<0.005	<1	8.53	19	458	<2	25	2.66	<4	16	55	21	3.37	0.30	23	1.54	669	<1	30	590	7	0.63	<5	7	<10	306	3161	19	116	22	18	46
178813	1360911	0.027	<1	8.02	25	337	2	6	1.44	<4	4	30	5	1.30	0.21	25	1.15	354	3	44	219	19	1.29	<5	16	10	102	1254	9	21	<10	6	146
178814	1360912	0.058	<1	7.88	28	328	2	26	1.07	10	4	34	9	1.50	0.06	27	0.98	322	5	53	216	14	1.80	<5	17	<10	94	1236	7	19	24	6	2117

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Derek Demianuk H.B.Sc., Laboratory Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, July 13, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/26/2012
 Date Completed: 07/13/2012
 Job #: 201242328
 Reference: TL 12 263
 Sample #: 69

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
178740	1360844	13	<0.001	0.013
178741	1360845	16	<0.001	0.016
178742	1360846	7	<0.001	0.007
178743	1360847	8	<0.001	0.008
178744	1360848	13	<0.001	0.013
178745	1360849	10	<0.001	0.010
178746	1360850	<5	<0.001	<0.005
178747	1360851	7	<0.001	0.007
178748	1360852	6	<0.001	0.006
178749	1360853	35	0.001	0.035
178750 Dup	1360853	71	0.002	0.071
178751	1360854	176	0.005	0.176
178752	1360855	45	0.001	0.045
178753	1360856	81	0.002	0.081
178754	1360857	52	0.002	0.052
178755	1360858	243	0.007	0.243
178756	1360859	52	0.002	0.052
178757	1360860	265	0.008	0.265
178758	1360861	20	<0.001	0.020
178759	1360862	13	<0.001	0.013
178760	1360863	20	<0.001	0.020
178761 Dup	1360863	18	<0.001	0.018
178762	1360864	32	<0.001	0.032
178763	1360865	56	0.002	0.056
178764	1360866	28	<0.001	0.028
178765	1360867	61	0.002	0.061
178766	1360868	808	0.024	0.808
178767	1360869	35	0.001	0.035
178768	1360870	<5	<0.001	<0.005
178769	1360871	270	0.008	0.270

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, July 13, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/26/2012
 Date Completed: 07/13/2012
 Job #: 201242328
 Reference: TL 12 263
 Sample #: 69

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
178770	1360872	13	<0.001	0.013
178771	1360873	<5	<0.001	<0.005
178772 Dup	1360873	7	<0.001	0.007
178773	1360874	<5	<0.001	<0.005
178774	1360875	11	<0.001	0.011
178775	1360876	11	<0.001	0.011
178776	1360877	7	<0.001	0.007
178777	1360878	13	<0.001	0.013
178778	1360879	7	<0.001	0.007
178779	1360880	2060	0.060	2.060
178780	1360881	22	<0.001	0.022
178781	1360882	12	<0.001	0.012
178782	1360883	60	0.002	0.060
178783 Dup	1360883	50	0.001	0.050
178784	1360884	492	0.014	0.492
178785	1360885	108	0.003	0.108
178786	1360886	149	0.004	0.149
178787	1360887	537	0.016	0.537
178788	1360888	377	0.011	0.377
178789	1360889	136	0.004	0.136
178790	1360890	6	<0.001	0.006
178791	1360891	335	0.010	0.335
178792	1360892	480	0.014	0.480
178793	1360893	232	0.007	0.232
178794 Dup	1360893	256	0.007	0.256
178795	1360894	306	0.009	0.306
178796	1360895	118	0.003	0.118
178797	1360896	117	0.003	0.117
178798	1360897	13	<0.001	0.013
178799	1360898	25	<0.001	0.025

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, July 13, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/26/2012
 Date Completed: 07/13/2012
 Job #: 201242328
 Reference: TL 12 263
 Sample #: 69

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
178800	1360899	16	<0.001	0.016
178801	1360900	5088	0.148	5.088
178802	1360901	70	0.002	0.070
178803	1360902	168	0.005	0.168
178804	1360903	166	0.005	0.166
178805 Rep	1360903	185	0.005	0.185
178806	1360904	14	<0.001	0.014
178807	1360905	168	0.005	0.168
178808	1360906	76	0.002	0.076
178809	1360907	17	<0.001	0.017
178810	1360908	320	0.009	0.320
178811	1360909	53	0.002	0.053
178812	1360910	<5	<0.001	<0.005
178813	1360911	27	<0.001	0.027
178814	1360912	58	0.002	0.058

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Tuesday, August 7, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 06/26/2012
 Date Completed: 07/13/2012
 Job #: 201242327
 Reference: TL 12 264
 Sample #: 93

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
178638	1360913	0.018	<1	4.98	15	512	<2	33	1.38	<4	7	35	6	0.97	0.48	15	0.77	252	<1	70	340	270	0.71	<5	7	<10	234	1362	6	28	<10	5	649
178639	1360914	<0.005	<1	4.59	8	372	<2	16	1.46	<4	5	32	12	0.88	0.17	11	0.69	236	<1	64	360	19	0.48	<5	<5	<10	186	1375	<2	26	<10	5	76
178640	1360915	0.006	<1	5.22	9	483	<2	34	1.58	<4	4	36	6	0.85	0.16	9	0.51	160	<1	73	379	18	0.45	<5	<5	<10	217	1340	8	27	<10	5	36
178641	1360916	<0.005	<1	3.46	3	407	<2	28	1.16	<4	4	30	7	0.80	0.21	7	0.49	155	<1	59	370	13	0.41	<5	<5	11	165	1312	3	27	<10	4	26
178642	1360917	0.009	<1	2.88	4	427	<2	33	1.05	<4	4	33	5	0.80	0.33	4	0.40	150	<1	68	362	15	0.45	<5	<5	<10	163	1257	3	26	<10	4	26
178643	1360918	0.009	<1	2.96	8	486	<2	7	0.71	<4	4	26	8	0.73	0.40	7	0.48	188	<1	49	369	16	0.33	<5	<5	<10	151	1323	3	26	<10	4	25
178644	1360919	0.012	<1	3.15	6	410	<2	21	0.65	<4	6	31	9	1.08	0.17	9	0.58	250	<1	63	397	16	0.61	<5	<5	<10	114	1358	4	26	<10	5	42
178645	1360920	0.234	<1	<0.01	440	>5000	<2	28	0.69	<4	7	16	36	2.85	0.21	<1	0.19	<100	3	15	<100	28	0.44	21	<5	<10	143	636	9	14	46	7	50
178646	1360921	0.016	<1	3.10	7	479	<2	27	0.50	<4	7	37	8	0.98	0.08	10	0.56	218	<1	79	342	16	0.54	<5	<5	<10	99	1417	4	25	<10	5	32
178647	1360922	0.023	<1	3.86	15	480	<2	34	1.09	<4	10	44	13	1.70	<0.01	11	0.89	527	<1	88	423	46	0.96	<5	<5	<10	115	1687	3	31	<10	6	71
178648D	1360922	0.027	<1	4.41	15	522	<2	26	1.19	<4	10	46	13	1.74	0.04	13	0.91	536	<1	90	441	50	0.98	5	<5	<10	126	1758	9	33	<10	7	73
178649	1360923	0.017	<1	4.42	<2	479	<2	29	2.21	<4	8	38	8	1.89	0.10	10	0.98	571	<1	74	451	21	0.66	<5	<5	<10	160	1760	5	33	<10	6	46
178650	1360924	0.013	<1	3.40	4	497	<2	55	1.16	<4	7	32	10	1.46	0.12	11	0.98	625	<1	63	585	17	0.57	<5	<5	<10	193	1820	7	35	<10	6	42
178651	1360925	0.019	<1	3.73	15	492	<2	23	0.96	<4	6	19	9	1.07	0.14	12	0.84	468	<1	41	554	29	0.57	<5	<5	<10	180	1752	2	34	<10	6	59
178652	1360926	0.026	<1	2.30	9	349	<2	38	0.86	<4	8	60	16	1.61	0.22	10	0.97	588	<1	74	575	27	0.74	<5	<5	<10	119	1742	<2	36	<10	6	91
178653	1360927	0.029	<1	3.12	15	320	<2	53	0.64	<4	4	25	10	0.91	0.46	2	0.50	405	<1	49	349	49	0.60	<5	<5	<10	154	1206	2	25	<10	4	73
178654	1360928	0.141	3	2.83	10	339	<2	33	0.66	<4	9	18	14	0.88	0.40	8	0.68	534	<1	37	350	319	0.68	<5	7	<10	144	1430	6	28	<10	4	626
178655	1360929	0.038	<1	3.17	15	274	<2	33	0.83	<4	7	15	14	0.71	0.55	6	0.63	469	<1	34	360	82	0.44	<5	<5	<10	132	1337	4	26	<10	4	228
178656	1360930	0.005	<1	1.90	2	281	<2	24	1.96	<4	15	49	24	3.27	0.35	6	1.35	676	<1	34	590	14	0.18	<5	<5	<10	208	2708	<2	106	12	16	67
178657	1360931	0.024	<1	3.91	14	330	<2	23	0.99	<4	5	20	11	0.91	0.42	9	0.82	606	<1	42	368	42	0.55	7	<5	<10	132	1515	4	27	<10	4	60

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/26/2012
 Date Completed: 07/13/2012
 Job #: 201242327
 Reference: TL 12 264
 Sample #: 93

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
178658	1360932	0.183	4	3.38	28	326	<2	16	0.37	<4	4	29	90	1.17	0.57	3	0.57	380	<1	48	321	469	1.05	<5	<5	<10	100	1355	3	24	<10	4	833
178659D	1360932	0.158	4	3.03	23	300	<2	31	0.27	<4	3	30	88	1.16	0.34	4	0.57	365	<1	51	317	466	1.04	7	6	<10	87	1259	3	22	<10	5	845
178660	1360933	0.029	<1	3.60	11	347	<2	29	0.63	<4	6	30	11	0.86	0.08	9	0.81	629	<1	54	368	40	0.50	<5	<5	<10	108	1452	2	25	<10	4	47
178661	1360934	0.021	<1	3.46	14	301	<2	32	0.90	<4	4	31	5	1.15	0.19	10	0.83	532	<1	60	366	25	0.60	<5	<5	<10	104	1456	8	26	<10	5	34
178662	1360935	0.012	<1	3.50	6	305	<2	25	1.73	<4	9	52	15	1.79	0.14	12	0.81	430	<1	55	417	15	0.67	5	<5	<10	213	1617	5	31	<10	6	31
178663	1360936	0.009	<1	3.75	4	320	<2	40	1.73	<4	9	52	16	1.84	0.10	13	0.80	427	<1	66	432	13	0.72	<5	<5	<10	217	1587	<2	32	<10	6	28
178664	1360937	0.008	<1	3.23	22	412	<2	18	1.17	<4	10	27	1	1.57	0.25	9	0.46	343	<1	58	395	15	1.44	<5	<5	<10	215	1365	2	27	<10	5	18
178665	1360938	0.008	<1	3.50	16	443	<2	38	0.39	<4	5	21	2	1.24	0.34	5	0.35	147	<1	42	371	12	1.31	<5	<5	<10	199	977	<2	24	<10	5	40
178666	1360939	0.009	<1	3.24	23	408	<2	12	0.21	<4	5	16	3	1.48	0.36	7	0.62	220	<1	38	378	10	1.48	5	5	<10	208	642	2	24	<10	5	43
178667	1360940	1.896	<1	2.46	3	353	<2	20	2.08	<4	17	54	33	3.90	0.61	6	1.45	754	<1	37	617	14	0.16	6	5	<10	238	2856	2	120	17	16	129
178668	1360941	0.012	<1	4.14	2	584	<2	43	1.16	<4	6	29	4	1.50	0.34	6	0.66	275	<1	55	360	18	0.98	<5	5	<10	312	988	3	29	<10	5	93
178669	1360942	0.019	<1	3.40	11	519	<2	41	0.51	<4	11	54	16	2.31	0.44	6	0.53	232	<1	60	437	20	1.96	<5	<5	<10	224	1423	5	45	<10	6	71
178670D	1360942	0.020	<1	2.82	15	483	<2	34	0.31	<4	11	52	16	2.35	0.20	8	0.56	234	<1	59	445	23	2.02	<5	<5	<10	161	1373	4	42	<10	7	68
178671	1360943	0.018	1	3.82	<2	504	<2	34	1.46	<4	17	104	34	3.14	0.43	17	1.17	523	<1	99	583	18	1.28	6	<5	<10	252	1950	12	68	<10	13	78
178672	1360944	0.016	1	3.19	<2	413	<2	27	1.96	<4	9	18	5	2.03	0.13	10	0.90	457	<1	36	592	29	0.64	<5	<5	<10	168	1846	5	36	<10	6	59
178673	1360945	0.013	2	4.55	37	582	<2	35	0.67	<4	9	34	12	1.69	0.14	9	0.58	768	<1	58	483	44	1.23	<5	<5	<10	156	1828	6	37	<10	6	130
178674	1360946	0.036	10	3.64	38	488	<2	22	0.51	<4	9	19	11	1.72	0.32	4	0.51	595	<1	40	451	59	1.44	<5	<5	<10	92	1646	<2	32	<10	7	113
178675	1360947	0.228	5	4.60	24	628	<2	28	0.49	<4	9	21	18	1.45	0.03	8	0.53	484	<1	39	484	129	1.16	<5	<5	<10	91	1716	3	34	<10	7	298
178676	1360948	0.116	4	4.83	36	579	2	35	1.12	<4	9	21	25	1.87	0.39	9	0.79	945	<1	37	482	119	1.47	<5	<5	<10	107	1790	3	37	<10	6	222
178677	1360949	0.119	4	4.45	30	478	2	22	0.74	<4	10	22	18	1.54	0.45	7	0.60	624	<1	39	505	48	1.01	5	<5	<10	97	1944	<2	39	10	6	242

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/26/2012
 Date Completed: 07/13/2012
 Job #: 201242327
 Reference: TL 12 264
 Sample #: 93

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
178678	1360950	0.009	<1	2.98	2	331	<2	37	2.16	<4	16	50	21	3.34	0.44	7	1.40	698	<1	34	596	9	0.18	<5	<5	<10	249	2911	<2	110	13	16	50
178679	1360951	0.040	1	4.15	<2	464	<2	32	0.83	<4	9	18	12	1.66	0.44	8	0.71	522	<1	32	491	35	0.57	<5	<5	<10	110	1978	6	38	<10	7	75
178680	1360952	0.024	<1	4.72	9	447	<2	13	1.27	<4	8	20	8	1.64	0.38	10	0.78	534	<1	33	478	31	0.73	<5	<5	<10	133	1942	7	37	<10	6	75
178681D	1360952	0.041	<1	4.32	<2	456	2	53	1.24	<4	8	19	9	1.68	0.29	8	0.76	551	<1	35	484	34	0.72	<5	<5	<10	129	1968	2	38	10	6	74
178682	1360953	0.017	<1	4.66	6	526	2	43	1.15	<4	8	19	7	1.73	0.15	10	0.73	484	<1	35	474	27	0.86	<5	5	<10	115	1958	3	37	<10	6	62
178683	1360954	0.009	<1	4.69	<2	678	2	27	2.71	<4	7	19	6	1.84	0.24	10	1.42	706	<1	33	481	39	0.28	5	<5	<10	136	1765	7	37	<10	6	77
178684	1360955	0.008	<1	4.55	<2	431	2	34	2.37	<4	7	21	12	1.70	0.09	10	1.36	663	<1	35	495	39	0.32	<5	6	<10	137	1803	2	36	<10	6	82
178685	1360956	0.010	<1	5.01	5	451	3	12	2.50	<4	7	23	13	1.74	0.06	11	1.42	693	<1	38	497	42	0.37	<5	<5	<10	144	1749	2	34	<10	6	94
178686	1360957	0.042	1	3.59	6	404	2	29	0.89	<4	8	19	20	1.22	0.05	5	0.70	309	<1	33	466	48	0.79	<5	<5	<10	112	1544	4	31	<10	6	156
178687	1360958	0.632	7	4.05	18	325	2	51	0.27	11	11	23	117	3.04	0.20	3	0.39	191	<1	39	379	217	2.86	5	<5	<10	75	1840	7	37	37	5	2908
178688	1360959	0.023	2	6.22	<2	591	2	33	2.97	<4	10	18	25	2.37	0.61	17	1.68	898	<1	30	642	67	0.83	<5	<5	<10	158	2254	3	44	<10	7	178
178689	1360960	5.351	67	1.78	32	388	<2	33	1.17	20	14	33	51	3.36	0.59	4	0.89	518	<1	30	529	617	0.47	41	<5	229	209	1816	2	90	50	13	1875
178690	1360961	0.014	<1	4.69	<2	490	2	25	2.46	<4	9	22	8	1.85	0.39	13	1.31	451	<1	38	492	36	0.56	<5	<5	<10	176	1963	<2	39	<10	6	73
178691	1360962	0.276	2	3.06	18	362	<2	41	<0.01	<4	6	29	46	1.75	0.57	2	0.30	<100	<1	44	366	30	1.74	<5	<5	<10	71	1524	3	30	<10	4	121
178692D	1360962	0.274	2	3.53	20	377	<2	28	<0.01	<4	7	30	47	1.84	0.41	3	0.32	<100	<1	46	379	34	1.81	<5	<5	<10	75	1609	4	32	<10	4	127
178693	1360963	0.025	<1	3.97	13	554	2	21	1.51	<4	8	22	6	1.71	0.70	11	0.95	444	<1	40	468	52	0.80	<5	<5	<10	131	1890	2	37	<10	5	141
178694	1360964	0.022	<1	5.37	12	613	2	34	2.11	<4	9	23	2	1.75	0.14	18	1.31	706	<1	37	591	71	0.56	<5	<5	<10	154	2268	2	43	<10	6	139
178695	1360965	0.081	2	4.82	19	940	2	26	1.46	<4	12	25	18	1.72	0.26	13	0.80	406	<1	43	405	86	1.08	<5	<5	<10	164	2092	6	40	<10	5	167
178696	1360966	0.078	1	4.98	13	546	2	20	1.25	<4	7	22	23	1.48	0.01	13	0.83	475	<1	38	479	61	0.87	<5	<5	<10	145	1886	<2	38	<10	7	110
178697	1360967	0.016	<1	5.81	9	526	<2	34	2.33	<4	8	24	8	1.86	0.14	16	1.18	497	<1	42	487	40	0.50	<5	<5	<10	173	1810	<2	37	<10	7	85

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/26/2012
 Date Completed: 07/13/2012
 Job #: 201242327
 Reference: TL 12 264
 Sample #: 93

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
178698	1360968	0.017	<1	5.60	<2	520	2	13	2.28	<4	8	27	3	1.81	0.29	13	1.15	389	<1	41	487	39	0.33	5	<5	<10	166	1930	3	38	<10	7	79
178699	1360969	0.086	<1	5.71	19	385	2	20	2.36	<4	8	34	9	1.99	0.15	17	1.35	618	<1	43	477	60	0.88	<5	5	<10	144	1821	8	40	<10	8	118
178700	1360970	0.007	<1	3.48	<2	325	<2	33	2.20	<4	16	52	22	3.34	0.42	9	1.42	696	<1	33	602	9	0.20	5	5	<10	251	2868	3	111	11	17	51
178701	1360971	1.007	4	4.21	33	378	2	37	0.66	<4	6	24	130	1.66	0.89	7	0.54	205	<1	41	409	595	1.41	<5	6	<10	111	1637	4	34	15	6	815
178702	1360972	0.515	2	3.73	91	339	2	33	0.53	4	18	117	146	3.09	0.40	6	0.57	291	<1	85	478	293	3.05	6	<5	<10	95	2205	5	77	11	11	775
178703R	1360972	0.470	3	3.56	80	385	<2	32	0.55	6	17	119	110	2.95	0.47	7	0.56	297	<1	84	463	362	2.94	7	<5	<10	94	2128	3	77	18	11	1290
178704	1360973	0.120	<1	4.54	39	436	2	44	1.92	<4	17	122	53	3.03	0.07	13	1.26	666	<1	82	481	87	1.20	<5	<5	<10	167	2280	2	70	<10	13	149
178705	1360974	0.072	<1	3.87	6	367	2	39	1.56	<4	22	125	45	3.79	0.08	14	1.36	657	<1	93	512	39	1.09	<5	<5	<10	137	2574	2	85	<10	15	89
178706	1360975	0.331	<1	3.27	70	359	2	28	0.58	<4	17	107	49	2.92	0.36	8	0.70	330	<1	83	479	121	2.12	<5	<5	<10	79	2272	6	70	<10	12	393
178707	1360976	0.376	<1	3.19	66	385	2	28	0.56	<4	18	117	60	2.80	0.28	8	0.70	319	<1	79	481	120	1.98	<5	<5	<10	76	2409	4	79	<10	11	310
178708	1360977	0.088	1	3.01	35	301	2	31	0.81	<4	11	59	48	1.86	0.29	6	0.73	336	<1	57	461	199	1.06	<5	<5	<10	79	1926	3	48	<10	8	176
178709	1360978	0.084	<1	5.02	9	343	2	39	1.83	<4	24	144	47	3.89	0.25	19	1.44	708	<1	87	507	55	1.09	<5	<5	10	126	3205	8	102	<10	14	87
178710	1360979	0.017	<1	3.08	<2	375	2	24	2.12	<4	8	24	11	1.79	0.24	9	1.14	422	<1	40	470	24	0.38	<5	<5	<10	128	1606	2	34	<10	5	98
178711	1360980	0.254	<1	<0.01	422	>5000	<2	19	0.58	<4	6	14	29	2.80	0.17	<1	0.15	<100	2	15	<100	21	0.39	19	<5	<10	132	459	9	13	39	6	25
178712	1360981	0.270	<1	3.48	8	333	<2	14	0.85	4	10	16	38	1.34	<0.01	8	0.78	261	<1	32	282	28	0.85	7	<5	<10	96	1236	3	22	16	5	1118
178713	1360982	0.066	<1	3.41	11	265	<2	33	0.62	<4	4	15	16	1.04	0.19	9	0.85	265	<1	31	225	44	0.58	<5	<5	<10	83	977	4	16	<10	4	83
178714D	1360982	0.067	<1	2.95	10	243	<2	24	0.59	<4	4	15	16	1.03	0.07	8	0.83	260	<1	29	217	38	0.60	<5	<5	<10	80	915	2	15	<10	4	87
178715	1360983	0.043	<1	3.37	3	277	<2	33	0.88	<4	4	14	8	1.03	0.09	10	0.94	283	<1	28	227	21	0.45	<5	<5	<10	89	939	3	15	<10	4	108
178716	1360984	0.030	<1	4.23	7	299	<2	36	1.11	<4	3	14	5	1.09	0.05	13	1.08	282	<1	26	228	22	0.43	<5	<5	<10	123	995	2	16	<10	5	81
178717	1360985	0.028	<1	2.73	<2	312	<2	41	0.16	<4	4	14	10	1.14	0.10	11	0.93	253	<1	31	240	18	0.64	<5	<5	<10	66	990	7	16	<10	4	44

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/26/2012
 Date Completed: 07/13/2012
 Job #: 201242327
 Reference: TL 12 264
 Sample #: 93

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
178718	1360986	0.075	<1	2.72	9	255	<2	38	0.16	<4	3	11	4	1.19	0.13	11	1.01	233	<1	28	246	16	0.91	<5	<5	<10	70	927	2	16	<10	4	61
178719	1360987	0.035	<1	2.87	11	298	<2	39	0.16	<4	4	10	6	1.08	0.18	13	1.20	296	<1	27	239	26	0.40	<5	<5	<10	66	1012	5	17	<10	4	51
178720	1360988	0.078	<1	3.85	16	312	<2	37	0.36	<4	4	9	6	0.92	0.06	14	0.98	220	<1	22	231	26	0.48	<5	<5	<10	81	978	4	16	<10	4	53
178721	1360989	0.136	<1	2.03	19	288	<2	35	0.18	<4	4	14	6	1.27	0.13	12	1.06	284	<1	32	214	16	0.90	7	7	<10	59	913	<2	17	<10	4	58
178722	1360990	0.008	<1	1.53	2	269	<2	51	1.96	<4	15	50	21	3.34	0.24	5	1.36	679	<1	34	601	8	0.17	<5	<5	<10	199	2605	4	108	10	16	55
178723	1360991	0.366	<1	3.16	28	327	2	31	0.22	11	4	16	36	1.80	0.27	18	1.19	320	<1	33	221	454	1.68	<5	6	<10	73	935	6	16	36	4	3382
178724	1360992	0.136	<1	2.39	28	283	<2	34	0.30	6	5	19	29	1.74	<0.01	14	1.29	313	<1	33	219	121	1.34	<5	<5	<10	73	891	4	16	16	4	1342
178725D	1360992	0.145	<1	2.81	18	309	<2	41	0.41	6	4	18	29	1.71	0.11	15	1.33	326	<1	31	220	125	1.31	<5	8	<10	81	926	3	17	16	4	1328
178726	1360993	0.106	1	3.46	18	369	<2	11	0.95	5	4	16	22	1.43	0.05	15	1.33	366	<1	28	234	377	0.94	<5	<5	<10	107	1002	4	17	16	4	1427
178727	1360994	0.027	<1	3.48	11	284	<2	45	0.96	<4	3	20	6	1.20	0.22	15	1.46	407	<1	38	229	36	0.54	<5	<5	<10	81	936	4	15	<10	4	77
178728	1360995	0.020	<1	4.43	9	306	<2	25	1.04	<4	4	15	6	1.11	<0.01	16	1.24	383	<1	25	233	28	0.67	<5	<5	<10	90	979	4	16	<10	5	53
178729	1360996	0.025	<1	4.41	10	266	<2	14	0.91	<4	4	16	7	1.14	<0.01	17	1.30	419	<1	29	229	28	0.76	<5	<5	<10	79	948	3	16	<10	5	62
178730	1360997	0.049	<1	3.47	35	250	<2	19	0.78	4	3	14	29	2.02	<0.01	12	1.14	367	<1	24	203	55	1.74	<5	<5	<10	70	882	2	14	11	4	859
178731	1360998	0.021	<1	3.57	6	262	<2	47	1.10	<4	3	11	11	1.57	0.11	21	2.13	464	<1	26	200	32	0.73	<5	<5	<10	76	910	3	15	<10	5	107
178732	1360999	0.013	<1	3.33	5	273	2	32	2.51	<4	4	11	14	1.39	<0.01	11	1.50	483	<1	26	203	34	0.58	<5	6	<10	96	844	2	15	<10	4	88
178733	1361000	1.989	<1	2.37	12	336	<2	37	2.01	<4	17	52	31	3.79	0.08	7	1.43	732	<1	38	620	14	0.18	<5	<5	<10	226	2744	5	116	15	16	63
178734	1361001	0.022	<1	4.24	8	301	<2	45	1.60	<4	3	13	5	1.31	0.25	14	1.67	480	<1	24	223	38	0.62	<5	<5	<10	91	926	4	15	20	5	104
178735	1361002	0.098	<1	3.88	4	236	<2	24	0.70	<4	4	14	5	1.45	0.46	29	2.48	466	<1	28	220	75	0.55	<5	5	<10	81	835	7	15	<10	4	332
178736D	1361002	0.097	<1	4.19	5	254	<2	19	0.74	<4	3	15	6	1.46	0.20	29	2.52	480	<1	25	219	85	0.55	<5	5	<10	84	888	2	16	<10	4	335
178737	1361003	0.074	<1	3.73	15	288	<2	38	0.60	<4	4	26	3	1.38	0.15	15	1.76	304	<1	50	191	21	0.70	<5	7	<10	88	923	2	17	<10	4	64

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/26/2012
 Date Completed: 07/13/2012
 Job #: 201242327
 Reference: TL 12 264
 Sample #: 93

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
178738	1361004	0.044	2	3.89	15	346	<2	26	1.20	<4	4	14	6	1.33	0.15	11	1.54	377	<1	26	226	1627	0.72	<5	6	<10	101	996	<2	16	<10	4	118
178739	1361005	0.059	<1	3.50	19	309	<2	34	2.72	<4	4	13	5	1.92	0.07	16	2.84	702	<1	25	218	156	0.93	<5	<5	<10	112	870	3	16	<10	5	790

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Friday, July 13, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/26/2012
 Date Completed: 07/13/2012
 Job #: 201242327
 Reference: TL 12 264
 Sample #: 93

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
178638	1360913	18	<0.001	0.018
178639	1360914	<5	<0.001	<0.005
178640	1360915	6	<0.001	0.006
178641	1360916	<5	<0.001	<0.005
178642	1360917	9	<0.001	0.009
178643	1360918	9	<0.001	0.009
178644	1360919	12	<0.001	0.012
178645	1360920	234	0.007	0.234
178646	1360921	16	<0.001	0.016
178647	1360922	23	<0.001	0.023
178648 Dup	1360922	27	<0.001	0.027
178649	1360923	17	<0.001	0.017
178650	1360924	13	<0.001	0.013
178651	1360925	19	<0.001	0.019
178652	1360926	26	<0.001	0.026
178653	1360927	29	<0.001	0.029
178654	1360928	141	0.004	0.141
178655	1360929	38	0.001	0.038
178656	1360930	5	<0.001	0.005
178657	1360931	24	<0.001	0.024
178658	1360932	183	0.005	0.183
178659 Dup	1360932	158	0.005	0.158
178660	1360933	29	<0.001	0.029
178661	1360934	21	<0.001	0.021
178662	1360935	12	<0.001	0.012
178663	1360936	9	<0.001	0.009
178664	1360937	8	<0.001	0.008
178665	1360938	8	<0.001	0.008
178666	1360939	9	<0.001	0.009
178667	1360940	1896	0.055	1.896

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, July 13, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/26/2012
 Date Completed: 07/13/2012
 Job #: 201242327
 Reference: TL 12 264
 Sample #: 93

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
178668	1360941	12	<0.001	0.012
178669	1360942	19	<0.001	0.019
178670 Dup	1360942	20	<0.001	0.020
178671	1360943	18	<0.001	0.018
178672	1360944	16	<0.001	0.016
178673	1360945	13	<0.001	0.013
178674	1360946	36	0.001	0.036
178675	1360947	228	0.007	0.228
178676	1360948	116	0.003	0.116
178677	1360949	119	0.003	0.119
178678	1360950	9	<0.001	0.009
178679	1360951	40	0.001	0.040
178680	1360952	24	<0.001	0.024
178681 Dup	1360952	41	0.001	0.041
178682	1360953	17	<0.001	0.017
178683	1360954	9	<0.001	0.009
178684	1360955	8	<0.001	0.008
178685	1360956	10	<0.001	0.010
178686	1360957	42	0.001	0.042
178687	1360958	632	0.018	0.632
178688	1360959	23	<0.001	0.023
178689	1360960	5351	0.156	5.351
178690	1360961	14	<0.001	0.014
178691	1360962	276	0.008	0.276
178692 Dup	1360962	274	0.008	0.274
178693	1360963	25	<0.001	0.025
178694	1360964	22	<0.001	0.022
178695	1360965	81	0.002	0.081
178696	1360966	78	0.002	0.078
178697	1360967	16	<0.001	0.016

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, July 13, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/26/2012
 Date Completed: 07/13/2012
 Job #: 201242327
 Reference: TL 12 264
 Sample #: 93

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
178698	1360968	17	<0.001	0.017
178699	1360969	86	0.003	0.086
178700	1360970	7	<0.001	0.007
178701	1360971	1007	0.029	1.007
178702	1360972	515	0.015	0.515
178703 Rep	1360972	470	0.014	0.470
178704	1360973	120	0.003	0.120
178705	1360974	72	0.002	0.072
178706	1360975	331	0.010	0.331
178707	1360976	376	0.011	0.376
178708	1360977	88	0.003	0.088
178709	1360978	84	0.002	0.084
178710	1360979	17	<0.001	0.017
178711	1360980	254	0.007	0.254
178712	1360981	270	0.008	0.270
178713	1360982	66	0.002	0.066
178714 Dup	1360982	67	0.002	0.067
178715	1360983	43	0.001	0.043
178716	1360984	30	<0.001	0.030
178717	1360985	28	<0.001	0.028
178718	1360986	75	0.002	0.075
178719	1360987	35	0.001	0.035
178720	1360988	78	0.002	0.078
178721	1360989	136	0.004	0.136
178722	1360990	8	<0.001	0.008
178723	1360991	366	0.011	0.366
178724	1360992	136	0.004	0.136
178725 Dup	1360992	145	0.004	0.145
178726	1360993	106	0.003	0.106
178727	1360994	27	<0.001	0.027

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Friday, July 13, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 06/26/2012
 Date Completed: 07/13/2012
 Job #: 201242327
 Reference: TL 12 264
 Sample #: 93

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
178728	1360995	20	<0.001	0.020
178729	1360996	25	<0.001	0.025
178730	1360997	49	0.001	0.049
178731	1360998	21	<0.001	0.021
178732	1360999	13	<0.001	0.013
178733	1361000	1989	0.058	1.989
178734	1361001	22	<0.001	0.022
178735	1361002	98	0.003	0.098
178736 Dup	1361002	97	0.003	0.097
178737	1361003	74	0.002	0.074
178738	1361004	44	0.001	0.044
178739	1361005	59	0.002	0.059

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/04/2012
 Date Completed: 07/18/2012
 Job #: 201242543
 Reference: TL 12 265
 Sample #: 73

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
190041	1361006	<0.005	<1	3.59	28	397	<2	18	0.65	<4	7	20	7	1.14	<0.01	6	0.59	306	<1	41	405	17	0.71	<5	<5	<10	89	1583	<2	34	<10	6	46
190042	1361007	0.006	<1	3.82	22	420	<2	19	0.24	<4	8	29	7	0.75	<0.01	6	0.50	213	<1	55	403	20	0.54	<5	9	<10	73	1489	<2	31	<10	5	26
190043	1361008	0.019	<1	3.89	30	406	<2	23	0.41	<4	9	31	10	0.72	<0.01	5	0.52	241	<1	40	404	26	0.58	<5	<5	<10	82	1481	<2	35	<10	6	120
190044	1361009	0.012	<1	1.67	22	356	<2	15	0.54	<4	9	43	15	0.84	<0.01	<1	0.50	306	<1	51	384	24	0.44	<5	<5	<10	83	1365	<2	34	<10	6	56
190045	1361010	<0.005	<1	1.82	15	312	<2	17	1.73	<4	13	40	16	2.70	<0.01	4	1.15	549	<1	27	482	8	0.25	<5	5	<10	215	2220	<2	94	14	13	49
190046	1361011	0.061	1	4.05	34	391	<2	16	1.37	<4	7	37	18	1.34	<0.01	10	0.85	470	<1	58	377	38	1.09	<5	7	<10	129	1474	<2	31	<10	6	72
190047	1361012	0.029	<1	2.96	36	434	<2	10	1.14	<4	3	30	7	1.03	<0.01	5	0.64	327	<1	56	304	37	0.81	<5	<5	<10	112	1105	3	22	<10	4	57
190048	1361013	0.050	<1	3.20	22	436	<2	20	1.98	<4	5	22	12	1.44	<0.01	6	0.96	634	<1	40	283	20	0.88	<5	<5	<10	117	1095	<2	22	<10	5	55
190049	1361014	0.157	4	3.16	25	380	<2	16	1.19	<4	5	18	27	0.99	<0.01	8	0.95	750	<1	37	480	137	0.67	<5	10	<10	116	1489	<2	26	<10	5	340
190050	1361015	0.217	1	3.97	30	420	<2	14	0.30	<4	5	21	14	1.06	<0.01	8	0.55	235	<1	43	457	132	1.10	<5	14	<10	101	1647	<2	28	<10	5	223
190051D	1361015	0.269	1	3.67	31	412	<2	18	0.25	<4	5	22	14	1.06	<0.01	7	0.53	223	<1	43	458	132	1.06	<5	13	<10	97	1610	<2	27	<10	5	223
190052	1361016	0.367	3	4.43	55	418	<2	22	0.32	<4	5	15	19	1.20	<0.01	9	0.54	218	<1	31	459	247	1.34	5	6	<10	104	1641	<2	28	<10	5	528
190053	1361017	0.152	2	4.40	50	521	<2	11	0.71	<4	5	23	15	1.37	<0.01	10	0.81	485	<1	43	472	253	1.37	<5	7	<10	125	1725	<2	30	<10	5	651
190054	1361018	0.015	<1	3.19	25	512	<2	14	0.92	<4	5	20	9	0.88	<0.01	8	0.75	369	<1	40	497	37	0.65	<5	5	<10	124	1550	<2	27	<10	5	57
190055	1361019	0.018	<1	3.02	23	534	<2	15	0.77	<4	6	31	15	1.04	<0.01	9	0.81	401	<1	38	475	84	0.73	<5	6	<10	112	1605	<2	29	<10	5	187
190056	1361020	4.560	55	2.66	41	401	<2	18	1.06	17	12	25	40	2.57	0.05	6	0.78	412	<1	21	435	480	0.61	48	<5	194	208	1653	<2	75	46	11	1495
190057	1361021	0.040	<1	1.77	23	282	<2	15	<0.01	<4	4	22	5	0.49	<0.01	1	0.40	136	<1	39	231	49	0.47	<5	<5	<10	70	1013	<2	23	<10	4	136
190058	1361022	0.050	<1	3.72	34	301	<2	<1	0.53	<4	4	19	4	0.91	<0.01	7	0.66	346	<1	32	297	65	0.91	<5	8	<10	100	1266	<2	28	<10	5	56
190059	1361023	0.016	<1	2.26	19	231	<2	17	0.61	<4	3	24	5	0.84	<0.01	7	0.69	438	<1	46	303	19	0.58	<5	<5	<10	84	1183	<2	21	<10	4	46
190060	1361024	0.057	<1	2.81	24	277	<2	15	1.04	<4	3	26	6	0.99	0.02	7	0.80	514	<1	48	285	18	0.62	<5	<5	<10	99	1186	<2	22	<10	4	43

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/04/2012
 Date Completed: 07/18/2012
 Job #: 201242543
 Reference: TL 12 265
 Sample #: 73

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
190061	1361025	0.052	<1	3.07	29	247	<2	11	0.21	<4	2	18	3	0.62	<0.01	5	0.50	215	<1	36	285	74	0.63	<5	7	<10	68	1246	<2	21	<10	4	227
190062D	1361025	0.099	<1	3.00	29	243	<2	11	0.21	<4	2	16	4	0.61	<0.01	5	0.49	205	<1	33	280	80	0.61	<5	6	<10	69	1236	<2	21	<10	4	231
190063	1361026	0.106	<1	2.25	41	233	<2	13	0.69	<4	3	23	4	0.98	<0.01	6	0.72	432	<1	41	264	36	0.88	<5	7	<10	78	1163	<2	22	<10	3	45
190064	1361027	0.197	<1	3.17	38	265	<2	16	0.61	<4	4	29	9	1.05	<0.01	8	0.69	419	<1	56	286	29	0.85	<5	9	<10	84	1220	<2	23	<10	4	108
190065	1361028	0.026	<1	3.07	22	242	<2	12	1.15	<4	4	18	10	1.07	<0.01	9	0.86	546	<1	35	282	18	0.67	<5	7	<10	94	1264	4	22	<10	4	89
190066	1361029	0.013	2	3.51	29	249	2	24	2.85	<4	9	28	7	1.86	<0.01	5	0.94	806	<1	56	307	19	1.10	<5	8	<10	204	1169	3	23	<10	5	57
190067	1361030	<0.005	<1	2.29	23	341	<2	7	1.84	<4	13	40	18	2.76	<0.01	4	1.17	559	<1	26	485	9	0.28	<5	6	<10	234	2184	<2	96	15	13	50
190068	1361031	0.105	15	3.11	45	256	<2	19	0.71	<4	7	20	29	2.00	<0.01	9	0.53	322	<1	36	312	175	1.82	<5	5	<10	135	1195	<2	23	<10	5	299
190069	1361032	<0.005	<1	3.14	42	277	<2	24	1.08	<4	6	15	2	1.55	<0.01	10	0.61	335	<1	32	322	19	1.63	<5	<5	<10	179	1249	<2	23	<10	5	46
190070	1361033	<0.005	<1	3.14	33	242	<2	18	2.40	<4	9	20	3	1.91	<0.01	3	0.77	517	<1	46	293	23	1.95	<5	8	<10	211	886	<2	22	<10	5	87
190071	1361034	<0.005	<1	2.60	39	234	<2	24	1.65	<4	7	22	<1	1.88	<0.01	8	0.90	514	<1	47	288	22	1.89	<5	6	<10	186	1034	<2	20	<10	4	69
190072	1361035	<0.005	<1	2.53	27	194	<2	8	1.56	<4	6	24	2	1.42	<0.01	8	0.88	423	<1	47	301	15	1.34	<5	11	<10	195	1017	<2	20	<10	4	33
190073D	1361035	<0.005	<1	2.71	21	192	<2	12	1.50	<4	5	23	2	1.35	0.03	9	0.86	403	<1	47	287	13	1.29	<5	<5	<10	187	994	<2	20	<10	4	33
190074	1361036	<0.005	<1	2.90	25	219	<2	24	1.50	<4	6	34	1	1.45	<0.01	10	0.87	413	<1	62	305	15	1.36	<5	8	<10	188	1063	<2	21	<10	4	31
190075	1361037	<0.005	<1	3.27	36	269	<2	16	1.14	<4	5	25	2	1.39	<0.01	9	0.72	318	<1	45	297	16	1.43	<5	7	<10	182	1189	<2	22	<10	5	36
190076	1361038	<0.005	<1	3.60	19	299	<2	13	1.25	<4	4	18	7	1.36	<0.01	10	0.89	393	<1	35	318	17	1.44	<5	6	<10	198	1222	<2	22	<10	5	46
190077	1361039	<0.005	<1	2.84	24	317	<2	10	0.59	<4	6	10	3	1.32	<0.01	8	0.59	187	<1	16	318	11	1.49	<5	9	<10	174	1216	<2	24	<10	5	21
190078	1361040	0.262	<1	<0.01	353	>5000	<2	15	0.49	<4	5	11	23	2.32	<0.01	<1	0.17	<100	<1	11	<100	18	0.50	13	<5	<10	81	434	<2	12	34	6	16
190079	1361041	0.008	<1	2.51	39	427	<2	21	0.68	<4	10	57	15	1.98	<0.01	9	0.61	240	<1	45	351	13	1.80	<5	7	<10	159	1388	<2	45	<10	8	29
190080	1361042	0.006	<1	2.07	19	440	<2	23	0.96	<4	15	77	31	2.63	<0.01	15	1.04	412	<1	50	422	16	0.96	<5	<5	<10	184	1721	<2	60	<10	9	61

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/04/2012
 Date Completed: 07/18/2012
 Job #: 201242543
 Reference: TL 12 265
 Sample #: 73

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
190081	1361043	0.006	<1	3.84	25	481	<2	7	1.46	<4	12	68	24	2.40	<0.01	14	0.99	474	<1	57	416	22	1.44	<5	10	<10	250	1661	<2	54	<10	9	75
190082	1361044	0.007	<1	3.09	29	398	<2	5	0.61	<4	6	28	4	1.64	<0.01	9	0.60	280	<1	41	349	15	1.44	<5	<5	<10	167	1316	3	29	<10	5	72
190083	1361045	<0.005	<1	2.89	55	389	<2	28	1.17	<4	7	49	9	1.69	<0.01	6	0.54	788	<1	65	399	21	1.65	<5	6	<10	173	1359	<2	37	<10	6	70
190084D	1361045	0.016	<1	3.21	55	415	<2	19	1.27	<4	8	49	9	1.71	<0.01	6	0.55	806	<1	64	405	21	1.65	<5	<5	<10	183	1385	<2	38	<10	6	68
190085	1361046	0.008	1	2.71	59	409	<2	19	0.46	<4	7	25	7	1.49	<0.01	4	0.42	566	<1	43	412	27	1.59	<5	8	<10	147	1448	<2	30	<10	5	80
190086	1361047	<0.005	<1	3.11	54	409	<2	21	1.64	<4	6	23	9	1.43	<0.01	8	0.80	902	<1	33	404	28	1.22	<5	<5	<10	177	1248	<2	31	<10	5	67
190087	1361048	<0.005	<1	3.38	47	234	<2	12	1.15	<4	5	26	5	1.30	<0.01	6	0.79	419	<1	37	358	19	0.88	<5	<5	<10	84	1283	<2	27	<10	5	48
190088	1361049	0.010	1	3.08	47	225	<2	14	0.51	<4	7	21	8	1.36	<0.01	3	0.54	328	<1	36	421	19	1.20	<5	8	<10	63	1330	<2	29	<10	5	77
190089	1361050	<0.005	<1	2.24	20	333	<2	19	1.77	<4	13	40	17	2.68	<0.01	4	1.14	543	<1	25	472	13	0.27	<5	<5	<10	230	2207	<2	94	15	13	46
190090	1361051	0.008	2	3.04	31	207	<2	19	0.90	<4	6	21	8	1.49	<0.01	3	0.80	613	<1	37	422	23	1.06	<5	7	<10	65	1217	<2	30	<10	5	65
190091	1361052	0.071	4	1.46	44	205	<2	16	<0.01	<4	6	22	36	1.33	<0.01	<1	0.40	180	<1	38	380	30	1.27	<5	7	<10	47	893	<2	26	<10	4	82
190092	1361053	0.083	2	1.68	37	283	<2	10	0.41	<4	6	25	10	1.23	<0.01	<1	0.53	217	<1	42	357	45	1.05	<5	<5	<10	64	817	<2	25	<10	4	97
190093	1361054	0.369	3	1.81	34	316	2	13	0.93	<4	7	19	32	1.70	<0.01	<1	0.83	371	<1	35	374	84	1.62	<5	<5	<10	88	744	<2	24	<10	4	240
190094	1361055	2.210	6	3.08	59	366	<2	26	0.26	8	6	33	66	1.62	<0.01	1	0.44	129	<1	53	379	162	1.82	12	<5	<10	86	827	<2	29	21	4	1963
190095D	1361055	1.875	5	2.11	68	347	<2	17	0.15	7	6	33	63	1.55	<0.01	<1	0.38	119	<1	53	353	153	1.67	13	<5	<10	77	771	<2	27	19	4	1857
190096	1361056	2.408	11	1.39	84	327	<2	17	0.11	6	6	29	214	1.53	<0.01	<1	0.33	100	<1	50	369	372	1.67	28	12	<10	70	719	<2	26	18	3	1458
190097	1361057	0.453	<1	1.76	45	330	2	9	0.09	<4	5	25	20	1.21	<0.01	<1	0.43	149	<1	46	369	80	1.17	<5	9	<10	58	825	<2	26	<10	4	167
190098	1361058	0.656	<1	2.62	46	334	<2	22	0.79	<4	6	25	20	1.31	<0.01	1	0.78	346	<1	44	386	72	1.05	<5	7	<10	71	979	<2	27	<10	5	130
190099	1361059	0.327	1	2.24	34	307	<2	10	0.91	<4	7	25	31	1.38	<0.01	3	0.80	379	<1	46	375	101	1.12	<5	<5	<10	60	1067	<2	26	<10	5	102
190100	1361060	2.439	<1	2.43	25	376	<2	21	1.84	<4	15	44	26	3.22	<0.01	6	1.26	614	<1	29	533	10	0.25	<5	<5	11	232	2338	<2	106	18	14	54

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/04/2012
 Date Completed: 07/18/2012
 Job #: 201242543
 Reference: TL 12 265
 Sample #: 73

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
190101	1361061	0.728	2	2.45	26	331	2	16	<0.01	<4	6	21	25	1.20	<0.01	1	0.37	107	<1	33	331	79	1.24	<5	<5	<10	53	1246	<2	28	<10	5	127
190102	1361062	0.058	<1	3.47	28	283	2	11	1.23	<4	6	20	9	1.35	<0.01	6	0.94	411	<1	31	397	50	0.92	<5	8	<10	85	1337	<2	29	<10	5	69
190103	1361063	0.056	<1	3.42	47	325	<2	16	0.50	<4	7	22	6	1.10	<0.01	5	0.52	161	<1	39	367	34	0.95	<5	5	<10	78	1452	<2	30	<10	5	75
190104	1361064	0.044	<1	3.42	23	353	<2	5	1.69	<4	6	20	22	1.45	<0.01	7	1.09	481	<1	33	396	35	0.77	<5	10	<10	95	1488	<2	30	<10	5	151
190105	1361065	0.682	1	2.26	43	379	2	14	0.70	<4	10	73	48	1.57	<0.01	2	0.65	308	<1	61	382	136	0.94	<5	<5	<10	68	1497	<2	47	<10	8	258
190106R	1361065	0.778	1	2.84	32	384	2	26	0.73	<4	10	84	48	1.66	<0.01	4	0.66	310	<1	79	386	126	1.05	<5	<5	<10	72	1555	<2	48	<10	9	237
190107	1361066	0.202	<1	2.70	28	292	<2	19	1.15	<4	16	121	32	2.54	<0.01	7	1.01	470	<1	83	422	34	1.07	<5	<5	<10	96	1979	<2	64	<10	12	68
190108	1361067	0.064	<1	2.95	14	270	<2	12	1.30	<4	17	112	36	2.99	<0.01	10	1.25	492	<1	72	424	34	0.83	<5	<5	<10	132	1953	<2	66	<10	12	61
190109	1361068	0.333	1	2.18	58	321	<2	7	0.22	<4	9	51	41	1.59	<0.01	2	0.48	166	<1	54	315	144	1.35	<5	<5	<10	69	1317	<2	40	<10	7	720
190110	1361069	0.183	<1	2.10	73	335	2	8	0.03	<4	9	46	46	1.82	<0.01	3	0.45	120	<1	52	367	71	1.88	<5	<5	<10	56	1288	<2	37	<10	6	573
190111	1361070	<0.005	<1	1.40	18	315	<2	11	1.73	<4	14	42	18	2.78	<0.01	2	1.17	555	<1	26	494	12	0.23	<5	5	<10	214	2142	4	97	12	13	60
190112	1361071	1.453	2	2.69	136	250	2	20	<0.01	24	15	82	321	3.73	<0.01	5	0.37	103	2	67	308	102	4.61	9	<5	<10	52	1360	<2	53	74	8	9452
190113	1361072	0.120	<1	3.17	54	321	<2	10	0.35	<4	10	54	36	1.64	<0.01	7	0.60	185	<1	47	339	40	1.58	<5	5	<10	69	1407	<2	42	<10	7	213
190114	1361073	0.070	<1	3.26	33	366	2	16	1.24	<4	8	32	9	1.48	<0.01	9	0.96	445	<1	37	399	40	0.89	<5	7	<10	87	1527	<2	37	<10	6	33
190115	1361074	0.375	5	2.90	66	334	<2	9	0.17	9	14	83	79	1.99	<0.01	7	0.55	201	<1	54	398	420	2.11	<5	<5	<10	57	1883	<2	63	30	9	2789
190116	1361075	0.030	<1	3.21	27	406	2	13	1.85	<4	7	30	32	1.61	<0.01	6	1.17	429	<1	51	407	30	0.54	<5	<5	<10	155	1513	<2	33	<10	5	105
190117D	1361075	0.021	<1	2.44	14	328	2	5	1.69	<4	6	28	30	1.51	<0.01	4	1.08	398	<1	49	390	28	0.51	<5	6	<10	142	1343	<2	30	<10	5	68
190118	1361076	0.013	<1	3.52	28	403	<2	17	1.91	<4	7	43	27	1.70	<0.01	7	1.20	444	<1	72	420	27	0.56	<5	<5	<10	162	1529	<2	34	<10	6	65
190119	1361077	0.028	<1	3.41	23	382	<2	9	0.78	7	3	19	18	1.01	<0.01	12	0.85	225	<1	38	195	22	0.68	<5	<5	<10	104	950	<2	15	16	5	1497
190120	1361078	0.007	<1	2.30	21	413	<2	16	0.62	<4	3	16	20	1.03	<0.01	11	0.90	251	<1	35	170	24	0.53	<5	7	<10	86	879	<2	14	<10	4	255

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/09/2012
 Date Completed: 07/23/2012
 Job #: 201242636
 Reference: TL 12 266
 Sample #: 310

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
196971	1361079	<0.005	<1	7.14	9	550	3	7	1.19	<4	6	19	7	1.37	<0.01	24	0.68	200	<1	26	385	8	0.44	<5	11	<10	522	1525	8	25	<10	8	50
196972	1361080	1.888	<1	6.19	13	478	2	8	2.37	6	19	63	37	4.09	<0.01	14	1.59	745	<1	33	675	11	0.47	<5	<5	<10	314	3089	9	126	21	19	50
196973	1361081	<0.005	<1	6.80	11	748	2	4	1.04	<4	4	19	9	1.31	<0.01	17	0.56	165	<1	29	387	5	0.41	<5	8	<10	653	1424	8	22	<10	8	27
196974	1361082	<0.005	<1	6.30	5	741	2	<1	1.03	<4	6	28	11	1.31	<0.01	17	0.54	175	<1	39	372	7	0.39	<5	<5	<10	604	1379	6	22	<10	8	28
196975	1361083	<0.005	<1	6.42	8	539	2	<1	1.46	<4	7	26	4	1.46	<0.01	20	0.69	211	<1	34	430	11	0.39	<5	7	<10	572	1494	3	27	<10	6	29
196976	1361084	<0.005	<1	6.40	5	737	2	<1	1.22	<4	5	40	9	1.25	<0.01	15	0.49	160	<1	39	374	11	0.40	<5	<5	<10	610	1358	9	20	<10	8	26
196977	1361085	<0.005	<1	6.15	3	546	2	1	1.25	<4	6	19	6	1.36	<0.01	19	0.62	183	<1	29	383	7	0.39	<5	5	<10	464	1429	6	23	<10	7	31
196978	1361086	<0.005	<1	6.48	9	536	2	<1	1.35	<4	6	44	8	1.44	<0.01	19	0.64	196	<1	41	379	8	0.36	<5	7	<10	490	1525	10	25	<10	6	45
196979	1361087	<0.005	<1	6.88	10	575	2	2	1.28	<4	6	22	5	1.47	<0.01	21	0.66	204	<1	32	395	8	0.37	<5	10	<10	503	1623	7	26	<10	7	31
196980	1361088	<0.005	<1	6.21	6	595	2	<1	1.29	<4	4	23	6	1.36	<0.01	16	0.58	181	<1	34	373	6	0.31	<5	5	<10	552	1392	11	23	<10	7	30
196981D	1361088	<0.005	<1	5.99	2	580	2	<1	1.26	<4	6	21	5	1.35	<0.01	17	0.58	180	<1	35	369	1	0.36	<5	7	<10	516	1375	12	22	<10	7	22
196982	1361089	<0.005	<1	7.55	3	391	2	4	1.29	<4	4	35	3	1.36	<0.01	20	0.71	184	<1	36	382	5	0.49	<5	6	<10	520	1278	5	25	<10	7	23
196983	1361090	<0.005	<1	6.87	6	407	<2	<1	1.45	<4	6	29	3	1.47	<0.01	17	0.73	193	<1	43	372	1	0.43	<5	9	<10	547	1269	7	26	<10	6	30
196984	1361091	0.016	<1	7.14	6	447	2	4	1.54	<4	5	38	4	1.47	<0.01	16	0.72	184	<1	56	386	8	0.42	<5	8	<10	554	1241	5	27	<10	6	26
196985	1361092	<0.005	<1	6.44	5	393	<2	2	1.46	<4	5	36	4	1.49	<0.01	13	0.64	193	<1	58	380	4	0.37	<5	11	<10	381	1287	6	27	<10	6	33
196986	1361093	<0.005	<1	1.85	2	216	<2	3	0.67	<4	4	18	3	1.06	<0.01	2	0.42	142	<1	34	270	<1	0.20	<5	<5	<10	258	838	9	19	<10	4	13
196987	1361094	<0.005	<1	3.47	3	238	<2	1	0.80	<4	4	32	3	1.17	<0.01	4	0.45	146	<1	52	280	5	0.27	<5	<5	<10	252	863	7	21	<10	4	12
196988	1361095	<0.005	<1	3.99	4	242	<2	<1	0.88	<4	4	22	3	1.14	<0.01	7	0.49	151	<1	31	307	2	0.30	<5	10	<10	248	943	2	21	<10	5	13
196989	1361096	<0.005	<1	4.15	3	247	<2	<1	0.85	<4	4	107	5	1.17	<0.01	8	0.52	162	<1	46	294	3	0.32	<5	6	<10	248	1002	4	21	<10	4	15
196990	1361097	<0.005	<1	3.59	4	186	<2	2	0.86	<4	4	26	4	1.02	<0.01	4	0.44	153	<1	27	245	4	0.35	<5	<5	<10	239	812	6	18	<10	4	12

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/09/2012
 Date Completed: 07/23/2012
 Job #: 201242636
 Reference: TL 12 266
 Sample #: 310

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
196991	1361098	<0.005	<1	5.52	7	269	<2	4	1.21	<4	6	29	5	1.51	<0.01	13	0.71	212	<1	44	385	6	0.33	<5	<5	<10	243	1185	5	26	<10	6	28
196992D	1361098	<0.005	<1	1.12	3	186	<2	1	0.49	<4	5	17	4	1.10	<0.01	2	0.49	156	<1	32	281	<1	0.20	<5	<5	<10	118	825	4	18	<10	4	14
196993	1361099	<0.005	<1	3.27	3	254	<2	<1	0.83	<4	5	15	7	1.13	<0.01	4	0.50	166	<1	18	295	2	0.24	<5	6	<10	195	1038	3	20	<10	4	17
196994	1361100	<0.005	<1	2.33	6	290	<2	3	1.38	4	11	36	18	2.39	<0.01	2	0.96	458	<1	18	434	2	0.27	<5	<5	<10	218	1787	5	78	13	12	23
196995	1361101	<0.005	<1	4.08	5	268	<2	<1	0.94	<4	5	14	4	1.30	<0.01	7	0.65	211	<1	17	315	2	0.34	5	<5	<10	263	1053	7	28	<10	6	20
196996	1361102	<0.005	<1	4.17	3	262	<2	3	0.95	<4	4	17	3	1.12	<0.01	6	0.49	173	<1	33	298	2	0.35	<5	12	<10	290	756	7	20	<10	5	16
196997	1361103	<0.005	<1	4.32	3	351	<2	<1	1.15	<4	5	12	5	1.21	<0.01	8	0.55	191	<1	22	387	4	0.36	<5	10	<10	348	884	7	23	<10	6	19
196998	1361104	0.013	<1	3.16	4	211	<2	<1	0.86	<4	5	18	7	1.14	<0.01	5	0.45	183	<1	29	273	7	0.34	<5	<5	<10	320	905	4	19	<10	4	24
196999	1361105	0.035	<1	2.90	2	237	<2	<1	0.76	<4	5	14	4	1.20	<0.01	4	0.47	185	<1	26	277	8	0.27	<5	<5	<10	220	892	5	19	<10	4	20
197000	1361106	0.018	<1	5.44	3	278	<2	<1	1.26	<4	5	18	4	1.46	<0.01	11	0.61	230	<1	28	336	8	0.36	<5	<5	<10	294	1171	5	24	<10	5	35
197001	1361107	0.011	<1	2.28	6	216	<2	<1	0.78	<4	5	18	8	1.27	<0.01	6	0.52	196	<1	30	268	3	0.24	<5	7	<10	178	785	<2	19	<10	4	21
197002	1361108	0.011	<1	6.73	7	266	<2	<1	1.33	<4	6	20	28	1.42	<0.01	17	0.73	223	<1	31	366	1	0.41	<5	5	<10	235	1323	4	26	<10	6	35
197003D	1361108	0.016	<1	3.82	2	198	<2	<1	0.83	<4	5	17	20	1.12	<0.01	8	0.55	177	<1	25	287	3	0.29	<5	<5	<10	178	960	4	20	<10	4	19
197004	1361109	0.010	<1	6.38	6	320	<2	<1	1.19	<4	7	23	6	1.42	<0.01	16	0.72	199	<1	29	371	5	0.42	<5	<5	<10	219	1446	13	25	<10	6	23
197005	1361110	0.011	<1	5.68	6	718	<2	1	1.44	<4	6	19	13	1.46	<0.01	15	0.72	220	<1	33	339	1	0.43	<5	<5	<10	290	1163	10	26	<10	6	24
197006	1361111	0.012	<1	3.75	2	358	<2	<1	1.19	<4	5	10	6	1.10	<0.01	7	0.50	154	<1	18	275	<1	0.33	<5	<5	<10	203	968	10	19	<10	5	12
197007	1361112	0.009	<1	4.06	8	369	<2	<1	1.40	<4	7	35	5	1.39	<0.01	8	0.57	208	<1	30	364	2	0.32	<5	7	<10	219	1466	5	30	<10	6	14
197008	1361113	0.019	<1	7.23	7	679	<2	<1	3.69	6	40	230	45	4.01	<0.01	31	1.71	635	<1	116	1123	9	0.42	<5	<5	<10	526	6507	11	133	<10	18	72
197009	1361114	0.007	<1	3.99	6	445	<2	<1	1.19	<4	8	26	3	1.45	<0.01	10	0.61	212	<1	30	349	<1	0.32	<5	<5	<10	288	1285	8	27	<10	5	15
197010	1361115	0.009	<1	6.78	4	680	<2	2	1.98	<4	10	40	4	1.91	<0.01	23	0.87	302	<1	39	457	1	0.44	<5	<5	<10	398	1957	<2	39	<10	8	22

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/09/2012
 Date Completed: 07/23/2012
 Job #: 201242636
 Reference: TL 12 266
 Sample #: 310

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
197011	1361116	0.010	<1	4.87	4	457	<2	1	1.70	<4	9	32	7	1.82	<0.01	15	0.75	347	<1	31	374	<1	0.37	<5	8	<10	300	1586	9	34	<10	7	24
197012	1361117	0.010	<1	4.28	3	416	<2	1	1.76	<4	7	70	9	1.46	<0.01	17	0.65	278	<1	48	338	2	0.34	<5	<5	<10	345	1285	7	29	<10	7	11
197013	1361118	0.009	<1	9.50	7	512	<2	1	2.57	<4	5	37	4	1.46	<0.01	29	0.70	222	<1	48	340	1	0.54	<5	<5	<10	475	939	6	23	<10	9	8
197014D	1361118	0.010	<1	4.05	2	328	<2	<1	1.45	<4	4	19	3	0.95	<0.01	11	0.44	152	<1	24	224	3	0.33	<5	5	<10	319	632	2	16	<10	5	<1
197015	1361119	0.011	<1	3.13	4	279	<2	<1	1.24	<4	3	41	2	0.94	<0.01	8	0.39	144	<1	37	210	<1	0.26	<5	7	<10	267	644	4	15	<10	5	2
197016	1361120	0.285	<1	<0.01	286	3185	<2	4	0.47	<4	6	12	26	2.19	<0.01	<1	0.21	<100	<1	9	<100	10	0.52	15	7	<10	131	707	13	12	31	7	2
197017	1361121	0.008	<1	3.17	36	686	<2	<1	1.15	<4	3	15	4	1.08	<0.01	7	0.35	122	<1	30	193	1	0.28	<5	8	<10	301	715	10	15	<10	5	<1
197018	1361122	0.008	<1	0.75	2	273	<2	2	0.69	<4	3	17	2	0.85	<0.01	3	0.37	114	<1	29	197	1	0.16	<5	<5	<10	261	561	4	13	<10	4	<1
197019	1361123	0.009	<1	1.06	<2	306	<2	<1	1.07	<4	3	17	2	0.95	<0.01	2	0.35	131	<1	33	197	1	0.17	<5	<5	<10	246	589	2	15	<10	4	<1
197020	1361124	0.011	<1	2.49	3	367	<2	<1	1.20	<4	4	15	2	0.95	<0.01	7	0.44	130	<1	28	217	<1	0.24	<5	<5	<10	275	659	3	15	<10	5	<1
197021	1361125	0.009	<1	3.10	4	266	<2	3	1.35	<4	2	17	2	0.96	<0.01	7	0.44	134	<1	33	229	3	0.27	<5	7	<10	283	663	2	15	<10	5	<1
197022	1361126	0.008	<1	3.05	<2	276	<2	<1	1.16	<4	2	22	3	0.99	<0.01	7	0.43	129	<1	45	228	2	0.26	<5	8	<10	272	667	5	16	<10	5	<1
197023	1361127	<0.005	<1	2.92	4	267	<2	4	0.92	<4	3	17	2	0.96	<0.01	7	0.39	117	<1	35	223	<1	0.26	<5	<5	<10	232	721	11	16	<10	5	<1
197024	1361128	<0.005	<1	1.83	5	250	<2	3	0.64	<4	3	17	2	0.90	<0.01	7	0.41	119	<1	34	203	2	0.23	<5	6	<10	191	681	9	15	<10	5	<1
197025D	1361128	<0.005	<1	3.46	4	356	<2	<1	1.04	<4	4	26	2	1.23	<0.01	15	0.57	164	<1	49	290	<1	0.28	<5	<5	<10	247	942	2	21	<10	6	5
197026	1361129	<0.005	<1	4.85	5	341	<2	2	1.58	<4	4	33	3	1.30	<0.01	20	0.58	202	<1	57	281	3	0.37	<5	7	<10	262	1021	9	20	<10	7	8
197027	1361130	<0.005	<1	4.74	3	337	<2	<1	1.60	<4	4	25	4	1.25	<0.01	19	0.57	200	<1	44	277	<1	0.35	<5	10	<10	285	994	7	20	<10	6	10
197028	1361131	<0.005	<1	3.02	2	243	<2	3	1.33	<4	3	16	3	1.13	<0.01	14	0.54	197	<1	29	251	5	0.30	<5	6	<10	230	807	9	17	<10	5	5
197029	1361132	<0.005	<1	1.40	4	232	<2	<1	0.72	<4	4	11	2	1.04	<0.01	11	0.55	197	<1	25	239	<1	0.23	<5	5	<10	171	772	8	16	<10	5	5
197030	1361133	<0.005	<1	2.25	<2	219	<2	<1	1.11	<4	3	21	3	1.10	<0.01	11	0.54	205	<1	42	240	<1	0.23	<5	5	<10	211	803	10	15	<10	5	7

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/09/2012
 Date Completed: 07/23/2012
 Job #: 201242636
 Reference: TL 12 266
 Sample #: 310

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
197031	1361134	<0.005	<1	2.93	3	481	<2	<1	1.39	<4	9	55	14	1.87	<0.01	25	0.86	272	<1	62	551	5	0.24	<5	<5	<10	409	1855	2	37	<10	8	22
197032	1361135	0.012	<1	4.07	3	379	<2	<1	1.82	<4	5	34	5	1.22	<0.01	16	0.51	223	<1	58	287	2	0.27	<5	<5	<10	297	989	8	20	<10	6	3
197033	1361136	<0.005	<1	4.66	3	365	<2	4	1.63	<4	4	18	4	1.19	<0.01	19	0.61	235	<1	26	277	4	0.32	<5	8	<10	311	989	6	18	<10	6	13
197034	1361137	<0.005	<1	0.44	2	321	<2	<1	1.20	<4	5	30	2	1.26	<0.01	11	0.51	236	<1	42	253	2	0.16	<5	5	<10	174	908	4	17	<10	5	11
197035	1361138	<0.005	1	4.08	9	425	<2	<1	1.58	<4	4	39	13	1.16	<0.01	8	0.36	183	<1	43	252	8	0.28	<5	<5	<10	290	996	5	19	<10	5	52
197036R	1361138	<0.005	<1	5.40	12	385	<2	<1	1.65	<4	4	23	12	1.06	<0.01	16	0.49	172	<1	26	254	5	0.39	<5	7	<10	304	973	6	18	<10	6	63
197037	1361139	<0.005	1	9.32	10	175	2	12	5.61	11	23	52	42	6.78	<0.01	23	1.96	2359	<1	70	494	2	0.51	<5	5	<10	314	3239	10	96	<10	13	58
197038	1361140	0.011	<1	5.42	8	412	<2	5	2.25	5	17	48	30	3.40	<0.01	11	1.40	662	<1	24	593	7	0.44	<5	6	<10	302	2917	7	108	16	18	75
197039	1361141	0.005	1	7.69	2	171	2	5	4.93	12	21	47	39	7.52	<0.01	25	1.86	2541	<1	67	431	12	0.55	<5	<5	<10	246	2840	13	88	<10	12	63
197040	1361142	<0.005	1	7.11	8	149	2	4	5.02	11	21	46	35	7.29	<0.01	21	1.87	2547	<1	62	412	8	0.52	<5	9	<10	238	2843	14	85	<10	11	52
197041	1361143	<0.005	<1	7.12	6	252	<2	9	5.26	9	21	46	25	5.81	<0.01	24	1.69	2071	<1	59	431	6	0.40	<5	<5	<10	284	3188	10	93	<10	10	49
197042	1361144	<0.005	1	6.49	10	207	2	8	5.11	9	22	76	21	5.75	<0.01	26	1.97	2050	<1	70	490	8	0.43	<5	7	<10	244	3634	10	92	<10	11	40
197043	1361145	<0.005	1	6.47	7	224	<2	2	5.51	8	26	125	30	4.74	<0.01	23	2.34	1359	<1	87	629	7	0.42	<5	5	<10	242	4164	15	97	<10	14	41
197044	1361146	<0.005	1	6.74	5	230	2	4	5.40	7	25	124	31	4.66	<0.01	21	2.34	1353	<1	82	615	6	0.44	<5	<5	<10	236	4141	13	95	<10	14	47
197045	1361147	<0.005	1	6.89	4	725	2	4	3.22	5	17	74	31	3.18	<0.01	27	1.33	710	<1	60	699	13	0.58	<5	5	<10	836	3245	11	71	<10	15	37
197046	1361148	<0.005	<1	3.45	5	279	2	9	2.61	5	18	64	31	3.16	<0.01	20	1.24	679	<1	52	622	2	0.43	<5	<5	<10	367	2358	14	66	<10	11	31
197047D	1361148	<0.005	1	6.84	10	393	2	5	3.74	6	23	83	40	4.11	<0.01	35	1.68	884	<1	67	831	7	0.58	<5	<5	<10	500	3653	16	86	<10	14	45
197048	1361149	<0.005	<1	5.29	3	162	<2	3	3.16	6	21	74	34	3.61	<0.01	18	1.44	768	<1	62	524	<1	0.46	<5	11	<10	223	2655	2	73	<10	13	37
197049	1361150	0.008	1	6.43	7	258	2	7	5.04	9	33	170	60	5.39	<0.01	25	3.39	859	<1	123	993	6	1.11	<5	<5	<10	346	4165	17	103	<10	17	88
197050	1361151	<0.005	<1	7.23	13	751	2	7	4.43	10	40	272	38	6.09	<0.01	55	1.92	1167	<1	130	1319	5	0.63	<5	7	<10	388	6206	8	143	<10	20	72

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/09/2012
 Date Completed: 07/23/2012
 Job #: 201242636
 Reference: TL 12 266
 Sample #: 310

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
197051	1361152	<0.005	<1	5.55	4	1054	<2	<1	1.06	<4	5	27	5	1.13	<0.01	24	0.79	213	<1	28	255	2	0.43	<5	9	<10	199	1002	8	14	<10	7	11
197052	1361153	<0.005	<1	7.49	10	871	<2	<1	1.14	<4	3	22	20	1.09	<0.01	29	0.80	253	<1	30	210	7	0.56	<5	8	<10	156	810	6	9	<10	8	20
197053	1361154	0.012	1	6.06	8	768	2	<1	1.30	<4	6	22	8	1.46	<0.01	23	0.68	315	<1	44	356	13	0.64	<5	<5	<10	324	1208	3	24	<10	11	45
197054	1361155	<0.005	2	7.16	<2	856	<2	6	0.97	<4	3	15	7	1.18	<0.01	22	0.60	264	<1	31	238	15	0.63	<5	<5	<10	213	948	<2	10	<10	9	31
197055	1361156	<0.005	2	7.16	4	750	<2	2	1.21	<4	5	18	4	1.20	<0.01	21	0.72	234	<1	33	303	13	0.60	<5	<5	<10	237	1263	5	17	<10	8	26
197056	1361157	<0.005	2	6.98	<2	645	2	<1	1.73	<4	7	23	4	1.59	<0.01	21	0.79	222	<1	40	480	9	0.56	<5	<5	<10	412	2153	8	35	<10	9	27
197057	1361158	<0.005	1	6.40	<2	716	2	<1	1.82	<4	7	17	6	1.79	<0.01	17	0.73	250	<1	32	583	9	0.47	<5	<5	<10	627	2401	<2	40	<10	10	39
197058D	1361158	<0.005	<1	5.67	2	689	2	<1	1.65	<4	8	25	7	1.72	<0.01	14	0.69	243	<1	31	575	12	0.42	<5	<5	<10	604	2377	6	38	<10	10	39
197059	1361159	<0.005	2	6.26	3	656	2	<1	1.89	<4	7	35	10	1.98	<0.01	16	0.65	272	<1	69	694	21	0.41	<5	<5	<10	773	2584	<2	43	<10	13	51
197060	1361160	5.091	70	5.27	32	486	<2	4	1.40	21	14	33	54	3.08	<0.01	13	0.91	491	<1	31	574	512	0.87	66	5	226	305	2206	7	86	44	17	1560
197061	1361161	<0.005	10	5.94	5	544	<2	8	1.94	4	9	22	11	2.05	<0.01	15	0.82	302	<1	30	522	58	0.56	5	<5	32	521	2275	<2	43	<10	11	173
197062	1361162	0.007	1	5.26	<2	383	<2	2	1.97	<4	8	22	10	1.74	<0.01	13	0.92	304	<1	32	471	5	0.46	<5	<5	<10	420	2239	5	36	<10	9	25
197063	1361163	<0.005	2	5.86	4	403	<2	3	2.41	<4	10	38	9	2.01	<0.01	17	1.23	402	<1	52	557	11	0.54	<5	<5	<10	410	2343	<2	46	<10	11	28
197064	1361164	<0.005	6	5.46	22	221	23	20	2.03	23	30	28	4	1.80	<0.01	14	0.95	313	<1	38	380	10	0.40	<5	19	<10	329	2058	18	60	<10	37	105
197065	1361165	<0.005	2	6.42	2	220	<2	<1	1.94	<4	10	30	6	1.86	0.03	13	0.89	301	<1	43	378	7	0.39	<5	<5	<10	333	2129	3	39	<10	7	25
197066	1361166	0.006	2	5.13	4	215	<2	5	1.77	<4	7	35	6	1.89	<0.01	10	0.86	304	<1	52	374	8	0.31	<5	<5	<10	307	2100	2	38	<10	6	24
197067	1361167	<0.005	<1	5.98	2	251	<2	<1	1.87	<4	9	34	6	1.76	0.01	12	0.75	251	<1	50	359	5	0.39	<5	5	<10	403	2056	5	36	<10	6	25
197068	1361168	<0.005	2	6.84	5	556	<2	4	1.86	<4	9	42	10	1.97	<0.01	14	0.81	265	<1	62	381	6	0.38	<5	<5	<10	538	2119	3	40	<10	7	33
197069D	1361168	<0.005	1	5.78	2	492	<2	4	1.57	<4	7	40	10	1.89	<0.01	17	0.82	255	<1	60	372	8	0.49	<5	<5	<10	394	1975	4	36	<10	8	31
197070	1361169	<0.005	1	5.00	<2	423	2	<1	1.87	<4	9	31	8	1.89	<0.01	9	0.72	285	<1	43	379	6	0.27	<5	<5	<10	398	2081	3	38	<10	6	46

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/09/2012
 Date Completed: 07/23/2012
 Job #: 201242636
 Reference: TL 12 266
 Sample #: 310

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
197071	1361170	<0.005	1	6.25	<2	340	3	2	1.94	<4	8	42	5	1.78	<0.01	14	0.69	254	<1	59	378	6	0.37	<5	<5	<10	339	2103	<2	37	<10	6	33
197072	1361171	<0.005	1	5.71	<2	279	2	2	1.82	<4	8	44	4	1.86	<0.01	14	0.66	278	<1	62	363	11	0.40	<5	<5	<10	321	2032	6	36	<10	7	27
197073	1361172	<0.005	3	6.17	<2	268	3	7	1.80	<4	8	28	12	1.67	<0.01	15	0.67	249	<1	39	379	5	0.46	<5	<5	<10	317	2115	5	33	10	7	24
197074	1361173	<0.005	2	5.60	<2	273	3	3	1.77	<4	7	28	8	1.58	<0.01	14	0.70	259	<1	42	378	<1	0.48	<5	5	<10	276	2032	3	33	17	7	24
197075	1361174	<0.005	1	5.27	6	412	4	4	1.80	<4	10	25	5	1.99	<0.01	19	0.92	326	<1	37	826	9	0.41	<5	<5	<10	481	2482	<2	42	<10	13	37
197076	1361175	<0.005	1	6.03	4	374	9	1	1.90	<4	8	35	5	1.96	<0.01	28	0.96	353	<1	57	620	5	0.39	<5	<5	<10	406	2299	6	40	<10	10	36
197077	1361176	<0.005	2	6.42	3	225	2	6	1.73	<4	7	36	31	1.74	<0.01	19	0.76	291	<1	56	397	10	0.43	<5	<5	<10	338	1948	3	36	<10	7	26
197078	1361177	<0.005	1	3.97	<2	405	2	<1	1.29	<4	7	33	8	1.67	<0.01	20	0.64	242	<1	55	392	7	0.40	<5	<5	<10	362	1863	3	33	<10	9	39
197079	1361178	<0.005	2	6.10	2	444	<2	4	1.31	<4	6	29	5	1.55	<0.01	19	0.59	215	<1	51	374	6	0.42	<5	<5	<10	429	1775	3	28	<10	9	35
197080D	1361178	<0.005	2	4.40	<2	409	<2	<1	1.09	<4	6	27	4	1.50	<0.01	15	0.54	207	<1	49	369	7	0.35	<5	<5	<10	365	1752	6	27	<10	8	32
197081	1361179	<0.005	<1	4.26	<2	490	2	3	1.02	<4	4	43	5	1.18	<0.01	14	0.39	148	<1	60	298	12	0.33	<5	<5	<10	516	1405	5	21	<10	8	33
197082	1361180	0.006	2	3.12	8	298	<2	2	2.06	<4	15	45	24	3.22	<0.01	10	1.27	619	<1	32	595	4	0.39	<5	<5	<10	239	2762	2	104	12	19	42
197083	1361181	<0.005	1	2.19	<2	400	<2	<1	1.01	<4	6	22	7	1.47	<0.01	15	0.56	216	<1	37	371	10	0.36	<5	<5	<10	342	1857	3	30	<10	10	35
197084	1361182	<0.005	1	6.17	<2	587	3	<1	1.19	<4	5	19	7	1.23	<0.01	22	0.47	159	<1	34	353	11	0.47	<5	<5	<10	553	1702	4	23	<10	9	33
197085	1361183	<0.005	2	6.80	<2	596	2	1	1.51	<4	5	28	6	1.42	<0.01	21	0.52	192	<1	49	373	11	0.51	<5	<5	<10	596	1698	8	23	10	11	39
197086	1361184	<0.005	2	5.07	<2	510	2	<1	1.16	<4	4	30	4	1.29	<0.01	16	0.45	164	<1	54	336	9	0.40	<5	<5	<10	467	1558	4	23	<10	9	33
197087	1361185	<0.005	2	6.53	<2	581	2	2	1.33	<4	4	24	3	1.22	<0.01	19	0.45	154	<1	47	351	8	0.49	<5	<5	<10	554	1634	2	22	<10	11	33
197088	1361186	<0.005	2	5.73	<2	666	<2	1	1.26	<4	5	30	4	1.25	<0.01	11	0.30	150	<1	46	354	11	0.40	<5	<5	<10	587	1644	<2	22	<10	10	35
197089	1361187	<0.005	2	5.95	6	660	2	<1	1.33	<4	5	38	5	1.27	<0.01	9	0.27	154	<1	57	348	6	0.44	<5	<5	<10	589	1639	2	23	<10	9	34
197090	1361188	<0.005	3	5.89	4	650	2	<1	1.33	<4	5	28	5	1.21	<0.01	8	0.28	151	<1	40	333	10	0.39	<5	<5	<10	588	1660	2	23	<10	9	44

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/09/2012
 Date Completed: 07/23/2012
 Job #: 201242636
 Reference: TL 12 266
 Sample #: 310

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
197091D	1361188	<0.005	2	5.81	4	648	2	<1	1.35	<4	5	26	5	1.21	<0.01	8	0.29	151	<1	36	331	6	0.35	<5	<5	<10	594	1626	3	23	<10	9	47
197092	1361189	<0.005	2	5.92	2	565	2	4	1.28	<4	6	27	6	1.27	<0.01	10	0.34	164	<1	32	334	7	0.40	<5	<5	<10	506	1737	2	25	<10	8	34
197093	1361190	<0.005	2	5.51	<2	595	<2	3	1.27	<4	5	27	3	1.26	<0.01	7	0.32	158	<1	37	334	4	0.34	<5	6	<10	502	1664	<2	24	<10	8	27
197094	1361191	<0.005	3	5.70	5	367	<2	4	1.26	<4	7	36	19	1.65	<0.01	16	0.52	221	<1	47	349	13	0.40	<5	<5	<10	262	1945	5	33	<10	6	24
197095	1361192	<0.005	2	5.61	5	324	<2	<1	1.81	<4	9	30	15	1.89	<0.01	11	0.61	274	<1	35	348	5	0.50	<5	<5	<10	230	1964	3	36	<10	6	26
197096	1361193	0.008	2	5.15	<2	315	<2	4	1.44	<4	9	34	35	1.70	<0.01	6	0.50	220	<1	36	485	6	0.58	<5	5	<10	262	1918	3	33	<10	7	22
197097	1361194	<0.005	2	5.08	2	307	<2	2	1.89	<4	9	33	16	1.97	<0.01	12	0.83	370	<1	39	371	14	0.53	<5	<5	<10	268	1876	4	34	24	6	34
197098	1361195	0.005	2	4.71	2	389	<2	<1	1.50	<4	8	30	5	1.72	<0.01	7	0.59	272	<1	36	367	4	0.42	<5	<5	<10	326	1884	2	34	<10	6	24
197099	1361196	<0.005	2	4.20	<2	349	<2	<1	1.48	<4	9	32	6	1.71	<0.01	3	0.47	225	<1	36	374	7	0.37	<5	<5	<10	259	1945	<2	35	<10	5	17
197100	1361197	0.011	1	5.40	5	435	<2	2	1.34	<4	8	35	15	1.62	<0.01	4	0.38	181	<1	41	389	5	0.41	<5	<5	<10	342	1977	<2	34	<10	6	21
197101	1361198	0.024	2	5.68	24	357	<2	5	1.19	<4	7	41	47	1.53	<0.01	4	0.38	205	<1	56	351	18	0.53	<5	<5	<10	318	1869	5	34	<10	6	172
197102R	1361198	0.016	2	5.95	4	392	<2	4	1.21	<4	8	46	18	1.69	<0.01	4	0.36	212	<1	65	362	6	0.56	<5	<5	<10	319	2009	7	35	<10	6	61
197103	1361199	0.010	2	6.15	5	546	<2	4	1.51	<4	7	35	6	1.65	<0.01	4	0.36	209	<1	43	412	10	0.47	<5	<5	<10	440	2046	3	34	<10	8	69
197104	1361200	1.960	4	5.05	6	484	<2	<1	2.09	4	17	57	33	3.67	<0.01	5	1.19	690	<1	36	611	9	0.42	<5	<5	<10	296	3195	3	116	24	19	65
197105	1361201	0.014	2	6.07	3	407	<2	<1	1.55	<4	9	107	11	1.88	<0.01	4	0.58	329	3	66	380	11	0.66	<5	<5	<10	347	2149	<2	46	<10	7	36
197106	1361202	0.400	2	7.08	2	272	<2	3	1.69	<4	6	84	242	1.72	<0.01	5	0.84	483	<1	78	306	67	0.72	<5	<5	<10	457	1589	<2	37	<10	5	115
197107	1361203	0.068	2	5.16	<2	405	<2	5	3.54	<4	9	74	83	2.46	<0.01	2	1.30	874	12	77	310	31	0.78	<5	<5	<10	633	1757	4	45	12	6	82
197108	1361204	0.016	2	4.74	2	425	<2	4	2.65	<4	8	47	28	1.99	<0.01	<1	0.97	624	2	57	333	15	0.56	<5	<5	<10	529	1856	5	39	<10	5	47
197109	1361205	0.015	2	5.13	<2	401	<2	<1	1.80	<4	6	35	14	1.64	<0.01	2	0.65	384	<1	41	345	13	0.62	<5	<5	<10	391	1863	5	34	<10	5	30
197110	1361206	0.012	1	4.75	4	379	<2	4	1.57	<4	8	36	12	1.60	<0.01	1	0.60	348	<1	46	334	13	0.60	<5	<5	<10	349	1800	6	32	<10	5	31

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/09/2012
 Date Completed: 07/23/2012
 Job #: 201242636
 Reference: TL 12 266
 Sample #: 310

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
197111	1361207	0.018	3	4.81	2	619	<2	<1	1.51	<4	8	44	13	1.66	<0.01	2	0.60	384	<1	58	367	19	0.63	<5	<5	<10	838	1809	2	36	<10	6	36
197112	1361208	0.028	2	4.45	5	415	<2	<1	1.50	<4	8	38	11	1.73	<0.01	3	0.68	539	<1	53	350	25	0.72	<5	<5	<10	421	1902	6	36	<10	5	153
197113D	1361208	0.033	2	3.88	5	353	<2	3	1.32	<4	7	45	9	1.48	<0.01	3	0.60	463	<1	60	323	22	0.78	<5	<5	<10	342	1683	4	32	<10	5	110
197114	1361209	0.036	2	5.37	10	484	<2	<1	1.07	<4	8	34	17	1.58	<0.01	6	0.43	589	<1	41	364	24	1.04	<5	<5	<10	327	1874	6	32	<10	6	42
197115	1361210	0.032	3	5.62	8	345	<2	<1	1.50	<4	7	30	25	1.55	<0.01	5	0.40	668	<1	35	362	28	1.03	<5	<5	<10	289	1893	4	32	<10	6	52
197116	1361211	0.038	2	5.59	8	357	<2	<1	1.52	<4	7	40	14	1.67	<0.01	5	0.34	522	<1	57	387	22	1.10	<5	<5	<10	279	1826	2	33	<10	6	36
197117	1361212	0.050	2	4.96	10	460	<2	<1	1.26	<4	8	51	11	1.74	<0.01	5	0.46	550	<1	77	362	18	1.14	<5	<5	<10	331	1796	5	31	<10	5	171
197118	1361213	0.028	3	4.43	7	344	<2	1	0.91	<4	5	37	<1	1.23	<0.01	6	0.47	433	<1	52	314	15	0.92	<5	<5	<10	321	1704	<2	30	<10	5	29
197119	1361214	0.050	3	5.19	8	422	<2	3	1.14	<4	6	47	9	1.52	<0.01	7	0.57	587	<1	75	342	12	0.69	<5	<5	<10	496	1887	6	32	<10	5	31
197120	1361215	0.058	3	5.02	9	790	<2	5	0.86	<4	6	37	4	1.54	<0.01	8	0.49	471	8	51	357	22	1.20	<5	<5	<10	1174	1781	<2	32	<10	5	44
197121	1361216	0.027	2	5.12	7	823	<2	3	1.16	<4	7	33	7	1.61	<0.01	6	0.44	410	<1	46	363	22	0.87	<5	<5	<10	774	1793	<2	30	<10	7	42
197122	1361217	0.045	2	5.01	6	753	<2	<1	1.30	<4	6	27	16	1.47	<0.01	7	0.32	306	<1	33	344	11	0.60	<5	<5	<10	590	1817	<2	28	<10	6	35
197123	1361218	0.019	2	5.00	10	545	<2	<1	1.63	<4	9	41	7	1.81	<0.01	8	0.36	394	<1	55	347	10	0.84	<5	<5	<10	309	1959	12	35	<10	5	27
197124D	1361218	0.030	2	4.84	8	505	<2	<1	1.58	<4	8	40	6	1.82	<0.01	8	0.36	395	<1	59	352	11	0.78	<5	<5	<10	279	1902	7	35	<10	5	25
197125	1361219	0.028	2	4.60	7	538	<2	3	1.37	<4	7	26	3	1.56	<0.01	5	0.36	296	<1	31	371	7	0.66	<5	<5	<10	369	1876	5	29	<10	6	27
197126	1361220	0.010	2	4.09	6	457	<2	2	2.22	4	17	57	24	3.47	<0.01	3	1.24	704	<1	35	629	4	0.35	<5	<5	<10	299	3047	5	116	21	19	43
197127	1361221	0.016	2	3.71	<2	437	<2	<1	1.56	<4	9	33	8	1.90	<0.01	6	0.49	357	<1	42	406	6	0.55	<5	<5	<10	316	2097	6	40	13	8	32
197128	1361222	0.023	2	3.91	7	538	<2	4	1.33	<4	7	26	27	1.72	<0.01	8	0.37	337	<1	34	367	10	0.64	<5	<5	<10	366	1897	<2	31	<10	6	33
197129	1361223	0.020	2	4.19	4	774	<2	<1	0.97	<4	6	27	15	1.44	<0.01	7	0.30	195	<1	38	402	12	0.36	<5	<5	<10	610	1853	<2	25	<10	8	38
197130	1361224	0.012	1	4.75	<2	707	<2	<1	1.30	<4	7	41	18	1.54	<0.01	7	0.31	258	<1	50	367	14	0.38	<5	<5	<10	552	1867	<2	28	<10	7	36

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

Treasury Metals Inc
Exchange Tower 130 King St Suite 3680
Toronto, On, CAN
M5X 1B1
Ph#: (416) 599-4133
Fax#: (416) 599-4959
Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/09/2012
Date Completed: 07/23/2012
Job #: 201242636
Reference: TL 12 266
Sample #: 310

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
197131	1361225	0.016	2	4.37	4	601	<2	6	1.25	<4	8	29	17	1.64	<0.01	9	0.31	333	<1	32	343	7	0.47	<5	<5	<10	391	1929	<2	30	<10	5	39
197132	1361226	0.023	<1	4.36	5	584	<2	4	1.24	<4	7	27	18	1.65	<0.01	10	0.32	341	<1	31	342	13	0.47	<5	<5	<10	380	1923	<2	30	<10	5	41
197133	1361227	0.014	3	4.74	7	801	<2	<1	1.06	<4	6	33	8	1.39	<0.01	8	0.27	211	<1	47	382	9	0.35	<5	<5	<10	682	1784	<2	25	<10	7	37
197134	1361228	0.034	2	3.63	8	735	<2	<1	0.94	<4	6	32	12	1.43	<0.01	7	0.31	268	<1	41	349	19	0.45	<5	<5	<10	617	1683	<2	25	<10	6	45
197135D	1361228	0.031	2	4.01	3	730	<2	<1	0.97	<4	6	29	12	1.43	<0.01	8	0.32	276	<1	39	356	23	0.52	<5	<5	<10	600	1723	3	25	<10	6	46
197136	1361229	0.009	2	4.51	5	811	2	1	1.13	<4	6	27	7	1.36	<0.01	10	0.28	201	<1	36	358	17	0.35	<5	<5	<10	647	1820	<2	25	<10	6	37
197137	1361230	0.009	4	4.21	2	736	<2	2	0.92	<4	5	25	5	1.27	<0.01	7	0.27	162	<1	29	374	9	0.39	<5	<5	<10	609	1823	<2	22	<10	8	33
197138	1361231	0.014	2	5.21	12	757	<2	5	1.16	<4	7	33	7	1.43	<0.01	11	0.31	213	<1	40	406	12	0.51	<5	<5	<10	626	1938	2	26	<10	9	36
197139	1361232	0.007	2	6.13	13	868	<2	<1	1.11	<4	5	30	4	1.34	<0.01	11	0.30	164	<1	33	425	15	0.51	<5	<5	<10	730	1961	<2	24	<10	10	40
197140	1361233	0.011	3	6.59	16	874	2	6	1.23	<4	5	35	7	1.49	<0.01	13	0.33	209	<1	45	437	13	0.49	<5	<5	<10	760	1937	2	26	<10	10	40
197141	1361234	0.017	3	5.37	13	705	<2	2	1.46	<4	8	43	12	2.00	<0.01	17	0.58	365	2	59	518	15	0.60	<5	<5	<10	570	2078	4	38	<10	10	44
197142	1361235	0.019	3	5.42	10	504	<2	2	1.43	<4	8	43	15	1.73	<0.01	14	0.47	447	<1	49	371	14	0.76	<5	<5	<10	389	1848	<2	35	<10	6	33
197143	1361236	0.029	4	5.50	5	465	<2	<1	1.32	<4	10	51	17	1.77	<0.01	11	0.44	379	1	60	358	25	0.81	<5	<5	<10	341	1921	4	36	<10	5	36
197144	1361237	0.045	5	4.89	10	563	<2	<1	1.14	<4	7	45	36	1.73	<0.01	10	0.48	711	<1	51	331	92	0.77	<5	<5	<10	443	1703	3	30	12	6	74
197145	1361238	0.362	92	5.58	23	617	<2	3	1.44	<4	8	45	42	2.07	<0.01	22	0.77	1738	5	51	380	149	1.23	<5	<5	<10	344	1943	8	36	<10	7	225
197146D	1361238	0.370	93	5.09	25	585	<2	2	1.36	<4	8	41	40	2.02	<0.01	21	0.79	1774	3	44	371	140	1.17	<5	<5	<10	325	1847	10	35	<10	7	219
197147	1361239	0.031	10	5.65	13	422	<2	2	1.05	<4	8	48	22	1.80	<0.01	15	0.68	1288	1	58	393	35	0.74	<5	<5	<10	242	1974	10	38	<10	7	65
197148	1361240	0.253	3	<0.01	264	>5000	<2	<1	0.64	<4	6	21	34	3.02	<0.01	<1	0.11	166	6	20	114	19	0.58	16	<5	<10	145	1017	6	17	36	8	15
197149	1361241	0.038	9	4.29	35	914	<2	<1	0.02	<4	8	33	17	1.46	<0.01	6	0.30	402	<1	33	389	45	0.66	<5	<5	<10	128	1781	<2	33	<10	7	44
197150	1361242	0.024	4	5.95	14	498	<2	<1	<0.01	<4	9	35	17	1.41	<0.01	8	0.35	486	<1	35	447	19	0.77	<5	<5	<10	156	2032	<2	39	<10	8	48

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/09/2012
 Date Completed: 07/23/2012
 Job #: 201242636
 Reference: TL 12 266
 Sample #: 310

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
197151	1361243	0.057	8	5.44	15	1147	<2	<1	<0.01	<4	9	35	12	1.10	<0.01	6	0.34	335	<1	38	432	31	0.95	<5	<5	<10	299	1823	4	37	<10	8	59
197152	1361244	0.165	20	6.55	19	1312	<2	3	0.26	<4	9	36	19	1.44	<0.01	10	0.42	539	27	34	426	80	1.42	<5	<5	<10	395	1974	2	37	<10	8	141
197153	1361245	0.793	70	5.71	23	604	<2	2	0.64	<4	10	42	33	1.98	<0.01	9	0.61	1272	<1	36	405	87	1.21	<5	<5	<10	213	1985	6	40	<10	7	157
197154	1361246	0.298	48	5.04	25	594	<2	<1	0.42	<4	9	42	27	1.97	<0.01	9	0.48	1011	<1	45	393	82	1.17	<5	<5	<10	182	2153	<2	42	<10	5	206
197155	1361247	0.024	8	5.02	8	430	<2	<1	0.18	<4	9	38	13	1.89	<0.01	9	0.39	779	<1	39	390	20	0.74	<5	<5	<10	151	2132	<2	42	<10	5	41
197156	1361248	0.019	5	5.61	33	314	<2	1	1.11	<4	10	36	15	1.92	<0.01	9	0.63	1045	<1	39	414	18	1.20	<5	<5	<10	194	2233	5	43	<10	6	34
197157D	1361248	0.019	7	3.98	45	275	19	16	0.96	19	25	27	14	1.51	<0.01	6	0.54	934	<1	33	359	15	1.07	<5	11	<10	188	1885	18	54	<10	30	91
197158	1361249	0.032	7	5.82	37	317	<2	1	1.54	<4	9	32	15	1.66	<0.01	11	0.52	1170	<1	36	394	28	1.48	<5	<5	<10	195	1941	3	39	<10	6	37
197159	1361250	0.053	11	4.90	31	385	<2	1	0.90	<4	7	24	12	1.55	<0.01	10	0.62	925	<1	32	414	70	1.62	<5	<5	<10	140	1842	<2	31	<10	6	109
197160	1361251	0.063	16	5.26	20	436	<2	<1	0.89	<4	5	26	8	1.45	<0.01	9	0.49	587	<1	36	396	86	1.63	<5	<5	<10	177	1817	<2	29	<10	5	133
197161	1361252	0.068	18	5.77	19	476	<2	<1	0.97	<4	6	48	37	1.41	<0.01	8	0.40	452	2	71	409	88	1.56	<5	<5	<10	166	1772	2	30	<10	6	157
197162	1361253	0.024	8	5.26	26	438	<2	<1	1.16	<4	6	30	16	1.37	<0.01	8	0.55	511	<1	36	397	44	1.46	<5	<5	<10	167	1748	5	28	<10	6	73
197163	1361254	0.027	4	6.37	27	441	<2	<1	1.54	<4	6	26	7	1.54	<0.01	9	0.58	487	<1	30	413	21	1.74	<5	<5	<10	207	1839	6	29	<10	7	48
197164	1361255	0.019	3	5.94	20	484	<2	2	1.96	<4	7	29	5	1.59	<0.01	10	0.61	533	2	31	389	17	1.53	<5	6	<10	213	1858	5	30	<10	6	44
197165	1361256	0.012	3	6.02	44	481	<2	1	2.13	<4	6	27	5	1.72	<0.01	10	0.80	641	<1	33	407	11	1.77	<5	<5	<10	239	1930	9	31	<10	6	41
197166	1361257	0.013	3	3.91	63	393	<2	<1	1.42	<4	5	25	49	1.31	<0.01	4	0.46	393	<1	31	342	29	1.54	<5	<5	<10	203	1535	7	25	<10	5	199
197167	1361258	0.028	3	5.19	24	591	<2	8	1.84	<4	6	35	16	1.51	<0.01	6	0.48	440	<1	47	409	25	1.73	<5	<5	<10	329	1826	5	29	<10	6	114
197168R	1361258	0.034	4	4.87	18	583	<2	3	1.75	<4	6	47	13	1.49	<0.01	5	0.46	413	<1	63	404	24	1.66	<5	<5	<10	335	1762	4	28	<10	5	93
197169	1361259	0.012	3	5.35	8	667	<2	1	1.59	<4	7	32	13	1.53	<0.01	6	0.47	283	<1	42	379	13	1.15	<5	<5	<10	588	1840	3	30	<10	6	46
197170	1361260	0.009	2	4.50	5	488	<2	<1	2.29	4	18	59	24	3.43	<0.01	3	1.24	707	<1	36	624	1	0.43	<5	<5	<10	331	3100	3	115	19	19	51

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/09/2012
 Date Completed: 07/23/2012
 Job #: 201242636
 Reference: TL 12 266
 Sample #: 310

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
197171	1361261	0.010	3	5.00	7	473	<2	<1	1.39	<4	7	33	12	1.46	<0.01	4	0.43	225	<1	38	407	8	0.77	<5	<5	<10	467	1940	4	39	<10	7	27
197172	1361262	0.010	2	4.90	9	421	<2	2	1.32	<4	8	200	15	1.50	<0.01	4	0.35	155	<1	76	406	5	1.23	<5	<5	<10	425	1742	2	33	<10	5	25
197173	1361263	0.011	3	5.03	10	426	<2	5	1.49	<4	7	57	17	1.62	<0.01	3	0.33	198	<1	51	412	9	1.15	<5	<5	<10	411	1674	3	29	<10	5	29
197174	1361264	0.009	3	5.99	9	540	<2	<1	1.74	<4	7	67	16	1.45	<0.01	5	0.33	241	<1	51	363	14	0.82	<5	5	<10	438	1729	<2	32	<10	6	50
197175	1361265	0.011	2	5.90	3	500	<2	<1	1.60	<4	8	35	19	1.51	<0.01	6	0.32	221	<1	45	387	9	1.13	<5	<5	<10	392	1673	<2	32	<10	6	29
197176	1361266	0.012	3	5.87	6	494	<2	5	1.63	<4	7	33	18	1.52	<0.01	6	0.32	222	<1	47	393	10	1.11	<5	<5	<10	394	1654	2	32	<10	6	34
197177	1361267	0.011	3	5.71	9	548	<2	1	1.25	<4	7	30	12	1.50	<0.01	4	0.32	155	<1	43	409	10	1.57	<5	<5	<10	319	1867	5	33	<10	6	30
197178	1361268	0.010	2	4.35	16	478	<2	3	0.68	<4	7	27	9	1.33	<0.01	4	0.26	108	<1	36	348	8	1.43	<5	<5	<10	277	1767	2	29	<10	5	19
197179D	1361268	0.011	3	5.52	14	524	<2	4	0.79	<4	7	29	9	1.39	<0.01	6	0.27	112	<1	41	370	8	1.48	<5	<5	<10	320	1880	<2	32	<10	6	19
197180	1361269	0.011	4	4.65	9	507	<2	1	1.29	<4	6	32	11	1.46	<0.01	6	0.27	167	<1	43	386	12	1.28	<5	<5	<10	302	1739	5	30	<10	5	24
197181	1361270	0.009	3	6.26	12	704	<2	<1	1.11	<4	8	32	6	1.50	<0.01	10	0.42	199	<1	38	520	13	1.07	<5	<5	<10	404	2024	4	35	<10	10	29
197182	1361271	0.012	4	5.73	9	570	<2	<1	1.30	<4	6	31	7	1.14	<0.01	9	0.31	221	<1	39	398	11	0.82	<5	6	<10	290	1946	2	31	<10	6	23
197183	1361272	0.010	3	6.67	4	580	<2	5	1.69	<4	7	31	16	1.36	<0.01	8	0.31	277	<1	37	427	17	0.91	<5	<5	<10	310	1849	3	30	<10	7	31
197184	1361273	0.011	4	6.21	10	566	2	5	1.73	<4	8	33	18	1.45	<0.01	7	0.35	297	<1	42	458	13	0.92	<5	<5	<10	308	1951	2	31	<10	6	33
197185	1361274	0.007	2	6.75	6	653	<2	2	1.94	<4	8	35	9	1.79	<0.01	11	0.50	353	<1	42	523	3	0.87	<5	<5	<10	398	2250	3	37	<10	8	42
197186	1361275	0.012	2	6.02	9	609	<2	<1	1.56	<4	9	33	13	1.48	<0.01	10	0.40	287	<1	45	451	10	0.92	<5	<5	<10	300	2088	2	35	<10	6	22
197187	1361276	0.014	3	7.20	22	676	<2	<1	1.83	<4	10	29	5	1.45	<0.01	12	0.47	285	<1	36	427	8	1.20	<5	<5	<10	310	2076	6	36	<10	6	21
197188	1361277	0.012	4	4.80	6	662	<2	<1	1.44	<4	8	28	9	1.38	<0.01	9	0.36	262	<1	37	385	11	1.04	<5	<5	<10	254	1875	4	31	<10	6	25
197189	1361278	0.014	4	4.61	16	615	<2	<1	1.45	<4	8	27	7	1.22	<0.01	8	0.26	213	<1	33	375	9	1.14	<5	<5	<10	289	1795	5	31	<10	5	20
197190D	1361278	0.015	3	4.62	19	649	<2	3	1.36	<4	9	28	8	1.37	<0.01	6	0.31	231	<1	38	413	6	1.19	<5	<5	<10	268	1898	2	31	<10	5	22

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/09/2012
 Date Completed: 07/23/2012
 Job #: 201242636
 Reference: TL 12 266
 Sample #: 310

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
197191	1361279	0.014	4	5.39	15	680	<2	<1	1.43	<4	10	32	10	1.35	<0.01	8	0.35	231	<1	44	433	8	1.00	<5	<5	<10	286	1942	2	33	<10	6	25
197192	1361280	4.898	75	3.21	40	521	<2	10	1.15	23	15	41	57	3.33	<0.01	1	0.76	526	<1	31	578	581	0.75	68	<5	252	238	2208	6	93	48	16	1719
197193	1361281	0.011	6	6.36	9	699	<2	2	1.69	<4	8	36	10	1.51	<0.01	9	0.36	283	<1	38	426	34	0.87	<5	<5	19	294	2034	4	38	<10	7	98
197194	1361282	0.013	4	7.40	5	780	<2	<1	1.82	<4	9	37	7	1.73	<0.01	13	0.34	363	<1	40	435	7	0.92	<5	<5	<10	319	2188	3	40	<10	7	29
197195	1361283	0.013	2	5.91	11	685	<2	<1	1.78	<4	8	33	9	1.56	<0.01	12	0.43	340	<1	39	409	8	1.07	<5	<5	<10	296	2003	3	35	<10	6	21
197196	1361284	0.014	3	5.69	11	570	<2	<1	1.64	<4	7	37	8	1.38	<0.01	11	0.42	331	<1	38	364	10	1.17	<5	<5	<10	263	1836	5	31	<10	6	31
197197	1361285	0.018	5	5.82	8	627	<2	3	2.10	<4	8	36	21	1.86	<0.01	16	0.86	592	<1	44	388	10	1.45	<5	<5	<10	289	1942	<2	34	<10	6	53
197198	1361286	0.017	3	6.52	8	578	<2	<1	2.37	<4	7	29	24	1.90	<0.01	23	1.08	665	<1	39	388	16	1.47	<5	<5	<10	309	1969	4	34	<10	7	55
197199	1361287	0.022	3	4.65	12	532	<2	<1	1.22	<4	7	27	9	1.44	<0.01	17	0.56	276	<1	37	351	14	1.69	<5	9	<10	265	1712	2	29	<10	5	102
197200	1361288	0.015	3	4.68	11	556	<2	2	1.21	<4	6	22	9	0.94	<0.01	16	0.61	301	<1	32	344	10	0.77	<5	<5	<10	249	1760	5	29	<10	5	24
197201D	1361288	0.017	2	6.87	9	668	<2	<1	1.49	<4	7	27	10	1.13	<0.01	23	0.73	342	<1	32	393	15	0.93	<5	<5	<10	277	1995	7	33	<10	6	28
197202	1361289	0.018	2	4.94	22	568	<2	<1	1.18	<4	9	31	12	1.24	<0.01	18	0.71	332	<1	48	389	14	0.98	<5	<5	<10	227	1789	9	30	<10	6	21
197203	1361290	0.018	3	6.49	27	613	<2	2	1.28	<4	8	30	6	1.32	<0.01	20	0.68	345	<1	38	402	11	1.38	<5	<5	<10	248	1963	3	32	<10	7	49
197204	1361291	0.017	3	6.61	27	565	<2	4	1.45	<4	7	25	7	1.31	<0.01	22	0.71	363	<1	32	385	11	1.40	<5	<5	<10	245	1845	6	30	<10	7	38
197205	1361292	0.017	1	7.31	19	513	<2	5	1.82	<4	7	25	10	1.44	<0.01	26	0.89	479	<1	28	389	11	1.37	<5	7	<10	252	1878	6	31	<10	8	33
197206	1361293	0.025	3	8.39	20	577	<2	7	1.49	<4	7	36	11	1.49	<0.01	28	0.74	334	<1	41	398	13	1.63	<5	<5	<10	279	1941	<2	33	<10	8	24
197207	1361294	0.024	2	>10.00	15	1374	3	2	2.76	<4	12	46	14	2.29	<0.01	38	1.05	521	<1	52	730	27	1.23	<5	<5	<10	1110	2378	3	47	<10	24	44
197208	1361295	0.037	2	8.66	16	632	<2	3	1.87	<4	7	39	11	1.46	<0.01	28	0.72	406	<1	44	426	19	1.38	<5	<5	<10	424	1991	4	34	<10	11	34
197209	1361296	0.029	5	5.98	15	589	<2	1	1.29	<4	7	31	9	1.38	<0.01	18	0.58	369	<1	38	341	12	1.48	<5	<5	<10	377	1770	5	31	<10	6	32
197210	1361297	0.024	4	7.37	15	1058	<2	10	1.98	<4	8	39	10	1.66	<0.01	21	0.64	388	<1	47	381	20	1.49	<5	<5	<10	547	1939	<2	33	<10	7	41

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/09/2012
 Date Completed: 07/23/2012
 Job #: 201242636
 Reference: TL 12 266
 Sample #: 310

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
197211	1361298	0.015	4	7.27	14	765	<2	<1	1.84	<4	8	38	11	1.66	<0.01	24	0.66	359	<1	46	455	12	1.14	<5	<5	<10	474	2145	6	36	<10	7	50
197212D	1361298	0.018	2	7.06	13	754	<2	3	1.84	<4	8	35	12	1.67	<0.01	25	0.66	359	<1	43	452	13	1.13	<5	<5	<10	480	2108	5	36	<10	7	49
197213	1361299	0.175	4	6.77	7	611	<2	<1	1.97	<4	8	35	12	1.63	<0.01	23	0.72	354	<1	44	393	15	0.80	<5	<5	<10	393	2050	<2	34	<10	7	48
197214	1361300	0.008	2	4.28	6	419	<2	3	2.14	<4	16	57	22	3.22	<0.01	9	1.33	663	<1	35	595	5	0.37	<5	<5	<10	291	2824	8	108	17	18	45
197215	1361301	0.099	2	5.32	7	1060	<2	1	2.15	<4	8	55	10	2.23	<0.01	19	0.99	582	<1	65	537	8	1.05	<5	<5	<10	462	2122	4	42	<10	9	45
197216	1361302	0.012	2	6.29	12	613	<2	6	1.58	<4	12	99	20	2.39	<0.01	27	0.84	688	<1	91	572	3	1.35	<5	<5	<10	332	2894	2	54	<10	10	32
197217	1361303	0.031	3	5.63	5	472	<2	4	1.29	<4	19	139	30	3.51	<0.01	26	0.80	935	<1	95	681	8	1.01	<5	5	<10	253	3595	7	70	<10	13	59
197218	1361304	0.024	4	7.51	6	471	<2	<1	1.90	<4	16	108	28	2.52	<0.01	30	0.92	718	<1	62	666	11	1.24	<5	<5	<10	321	3514	3	62	<10	12	36
197219	1361305	0.035	2	8.25	29	463	<2	<1	1.62	<4	10	37	11	1.82	<0.01	29	0.93	541	<1	41	406	23	1.79	<5	<5	<10	302	2060	4	36	<10	9	38
197220	1361306	0.035	2	7.13	15	451	<2	1	1.49	<4	8	46	9	1.57	<0.01	26	0.98	605	<1	69	408	20	1.28	<5	<5	<10	270	2017	<2	35	<10	8	38
197221	1361307	0.053	2	6.20	26	592	<2	<1	1.76	<4	10	61	23	1.67	<0.01	21	0.92	765	<1	43	424	17	1.31	<5	<5	<10	254	2156	7	47	<10	9	27
197222	1361308	0.057	2	6.76	19	537	<2	4	1.43	<4	9	32	10	1.35	<0.01	27	0.91	516	<1	40	364	21	1.23	<5	<5	<10	266	1964	<2	33	<10	7	38
197223D	1361308	0.059	3	7.21	19	559	<2	<1	1.50	<4	7	32	9	1.38	<0.01	29	0.96	524	<1	42	375	24	1.25	<5	<5	<10	275	1981	3	33	<10	7	37
197224	1361309	0.062	2	7.24	23	655	<2	<1	1.50	<4	10	46	15	1.54	<0.01	30	0.90	563	<1	39	400	25	1.38	<5	<5	<10	280	2083	8	39	<10	8	47
197225	1361310	0.050	2	7.21	19	544	<2	3	1.89	<4	8	28	16	1.63	<0.01	31	1.11	781	<1	35	410	29	1.06	<5	<5	<10	341	2110	3	35	<10	7	44
197226	1361311	0.142	3	5.53	11	425	<2	12	1.24	<4	15	83	41	2.65	<0.01	26	1.18	694	<1	62	474	28	1.60	<5	<5	<10	260	2352	<2	60	<10	12	60
197227	1361312	0.051	1	5.79	15	408	<2	1	1.16	<4	8	36	14	1.61	<0.01	24	1.07	534	<1	41	361	32	1.07	<5	<5	<10	256	1807	9	32	<10	8	62
197228	1361313	0.071	2	4.87	13	352	<2	<1	0.75	<4	6	33	3	0.85	<0.01	20	0.90	586	<1	43	368	29	0.71	<5	<5	<10	216	1663	3	28	<10	6	57
197229	1361314	0.176	3	5.92	25	470	<2	3	0.94	<4	8	31	3	0.88	<0.01	25	0.87	628	<1	37	377	33	0.82	<5	<5	<10	292	1774	6	29	<10	7	49
197230	1361315	0.064	2	6.65	15	989	2	1	1.43	<4	6	32	14	1.28	<0.01	26	0.68	393	<1	36	485	25	0.67	<5	<5	<10	785	1706	2	27	<10	13	44

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/09/2012
 Date Completed: 07/23/2012
 Job #: 201242636
 Reference: TL 12 266
 Sample #: 310

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
197231	1361316	0.037	2	4.73	28	937	2	6	1.18	<4	6	35	40	1.30	<0.01	21	0.63	317	<1	38	504	41	0.52	<5	<5	<10	713	1608	6	26	<10	11	227
197232	1361317	0.136	3	4.43	19	582	<2	2	0.76	<4	7	33	11	1.04	0.07	25	0.84	621	<1	47	410	31	0.77	<5	<5	<10	281	1823	4	31	<10	5	113
197233	1361318	0.017	4	6.34	9	1307	5	<1	2.10	<4	8	43	19	2.00	<0.01	23	0.83	534	<1	67	686	35	0.62	<5	<5	<10	1155	1995	4	38	<10	17	97
197234R	1361318	0.013	4	6.82	4	1416	3	<1	2.27	<4	8	34	14	2.02	0.15	25	0.83	483	<1	49	670	39	0.60	<5	<5	<10	1240	2071	2	38	<10	19	70
197235	1361319	0.103	3	6.05	10	929	4	<1	1.43	<4	7	36	17	1.41	<0.01	30	0.82	639	<1	54	478	40	0.83	<5	<5	<10	610	1702	5	29	<10	10	96
197236	1361320	1.960	5	5.19	9	466	<2	2	2.20	4	16	54	33	3.81	<0.01	12	1.40	725	<1	37	644	15	0.46	<5	<5	<10	299	3181	8	118	23	19	79
197237	1361321	0.088	5	6.32	10	851	4	<1	1.60	<4	8	32	23	1.65	0.03	27	0.93	642	<1	40	487	41	0.80	<5	<5	<10	618	1845	6	38	<10	11	90
197238	1361322	0.109	3	4.60	4	718	<2	2	1.08	<4	5	27	16	1.07	<0.01	30	1.13	920	<1	33	364	38	0.55	<5	<5	<10	311	1582	5	28	<10	5	67
197239	1361323	0.040	3	6.16	21	1099	2	2	1.69	<4	9	40	12	1.67	<0.01	33	0.88	466	<1	43	567	29	0.63	<5	<5	<10	890	1928	7	34	<10	12	47
197240	1361324	0.164	5	5.98	15	745	<2	<1	1.08	<4	7	36	25	1.00	<0.01	31	0.79	514	<1	53	413	70	0.65	<5	<5	<10	392	1873	4	32	<10	7	158
197241	1361325	0.084	3	6.43	16	504	<2	3	0.81	<4	7	34	24	0.88	<0.01	30	0.78	532	<1	52	388	35	0.84	<5	<5	<10	237	1808	3	31	<10	6	61
197242	1361326	0.069	3	6.33	15	496	<2	<1	0.82	<4	8	31	23	0.92	<0.01	31	0.82	579	<1	49	381	35	0.90	<5	<5	<10	229	1902	5	31	<10	6	68
197243	1361327	0.092	6	4.10	41	520	18	14	0.32	17	22	35	20	0.79	<0.01	24	0.61	360	<1	58	355	32	0.90	<5	18	<10	183	1671	14	46	<10	28	145
197244	1361328	0.195	4	6.68	20	589	<2	2	0.90	<4	8	36	12	1.22	<0.01	33	0.91	657	<1	52	392	31	1.30	<5	<5	<10	258	1867	4	32	<10	7	86
197245D	1361328	0.194	3	6.69	16	579	<2	6	0.94	<4	7	34	11	1.22	<0.01	32	0.87	652	<1	50	378	38	1.27	<5	<5	<10	262	1768	3	31	<10	7	81
197246	1361329	0.054	3	6.92	8	322	<2	<1	0.59	<4	6	34	10	0.67	0.04	20	0.59	344	<1	49	390	38	0.81	<5	<5	<10	244	1450	<2	26	<10	7	19
197247	1361330	0.024	2	7.14	7	1152	2	<1	1.57	<4	5	26	14	1.32	<0.01	26	0.56	317	<1	35	484	41	0.62	<5	<5	<10	975	1588	3	25	<10	13	36
197248	1361331	1.657	2	6.55	14	414	2	<1	0.89	<4	7	34	12	0.99	<0.01	26	0.76	540	<1	48	390	55	0.99	<5	<5	<10	289	1581	5	30	<10	7	60
197249	1361332	3.171	3	6.86	11	489	6	<1	0.58	<4	7	30	14	0.94	<0.01	32	0.69	447	<1	38	404	112	1.00	<5	<5	<10	212	1766	2	31	<10	6	124
197250	1361333	0.139	2	6.87	19	481	2	3	0.84	<4	10	36	4	1.39	<0.01	35	0.75	532	<1	54	391	69	1.45	<5	<5	<10	241	1880	5	33	<10	7	66

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/09/2012
 Date Completed: 07/23/2012
 Job #: 201242636
 Reference: TL 12 266
 Sample #: 310

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
197251	1361334	0.102	3	6.78	32	480	<2	3	1.36	<4	10	49	18	1.73	<0.01	33	0.96	766	<1	57	409	42	1.42	<5	<5	<10	265	1953	7	39	<10	8	66
197252	1361335	0.121	5	6.22	10	811	4	4	1.47	<4	6	26	20	1.44	<0.01	32	1.02	967	<1	33	351	37	1.04	<5	<5	<10	260	1567	9	36	<10	7	159
197253	1361336	0.089	3	7.47	13	672	6	3	1.39	<4	5	30	16	1.29	<0.01	39	0.94	788	<1	37	378	43	1.01	<5	<5	<10	286	1378	4	29	<10	7	210
197254	1361337	0.007	2	6.91	2	463	5	<1	1.21	<4	4	23	1	0.81	<0.01	33	0.63	254	<1	31	316	17	0.60	<5	<5	<10	277	1149	6	26	<10	6	31
197255	1361338	0.006	2	7.03	4	416	<2	<1	1.25	<4	3	26	<1	0.81	<0.01	30	0.60	189	<1	33	296	7	0.71	<5	<5	<10	259	941	2	23	<10	7	5
197256D	1361338	<0.005	2	7.98	6	461	2	5	1.48	<4	3	28	<1	0.89	<0.01	32	0.64	204	<1	35	320	11	0.76	<5	<5	<10	284	990	<2	25	<10	7	8
197257	1361339	<0.005	<1	6.67	6	524	<2	<1	1.11	<4	5	24	<1	0.93	<0.01	29	0.67	209	<1	31	319	5	0.71	<5	<5	<10	306	938	<2	25	<10	7	8
197258	1361340	<0.005	3	5.55	5	422	<2	4	2.22	<4	15	54	22	3.23	<0.01	13	1.34	663	<1	33	603	8	0.41	<5	<5	<10	308	2991	6	108	18	19	40
197259	1361341	<0.005	<1	6.94	3	502	<2	3	1.53	<4	4	29	1	1.26	<0.01	32	0.78	259	<1	34	334	4	0.67	<5	<5	<10	334	1232	7	33	<10	8	10
197260	1361342	<0.005	1	7.65	7	519	<2	<1	1.53	<4	3	25	<1	1.09	<0.01	39	0.64	184	<1	33	315	8	0.70	<5	<5	<10	352	1036	3	25	<10	7	8
197261	1361343	<0.005	1	6.56	<2	552	<2	2	1.88	<4	3	27	<1	1.25	0.09	35	0.62	199	<1	37	305	6	0.45	<5	<5	<10	320	1181	5	25	<10	6	10
197262	1361344	<0.005	3	7.62	<2	519	3	5	1.96	<4	4	27	<1	1.12	<0.01	42	0.56	224	<1	33	307	6	0.65	<5	<5	<10	314	1196	4	24	<10	7	10
197263	1361345	<0.005	2	7.19	<2	470	4	2	1.88	<4	4	23	<1	1.19	<0.01	46	0.60	267	<1	30	326	5	0.56	<5	<5	<10	299	1280	3	26	<10	7	13
197264	1361346	<0.005	3	8.19	7	464	5	<1	2.12	<4	5	26	<1	1.29	<0.01	49	0.66	293	<1	35	368	5	0.64	<5	<5	<10	310	1358	6	26	<10	8	14
197265	1361347	<0.005	2	6.78	6	430	3	2	2.37	<4	4	29	<1	1.51	<0.01	41	0.65	338	<1	41	361	7	0.53	<5	<5	<10	310	1309	<2	26	<10	9	17
197266	1361348	<0.005	1	7.11	<2	404	<2	<1	1.85	<4	5	24	<1	1.47	<0.01	42	0.71	311	<1	31	386	5	0.46	<5	<5	<10	322	1332	9	23	<10	9	16
197267D	1361348	<0.005	<1	8.74	4	396	<2	4	1.84	<4	5	28	<1	1.42	<0.01	45	0.77	295	<1	31	386	5	0.64	<5	5	<10	321	1289	3	23	<10	11	14
197268	1361349	<0.005	3	8.36	3	353	<2	8	1.99	<4	4	80	<1	1.60	<0.01	45	0.84	343	<1	41	389	4	0.59	<5	<5	<10	330	1204	2	22	<10	11	18
197269	1361350	0.006	2	9.94	<2	407	<2	3	2.09	<4	6	29	<1	1.30	<0.01	50	0.68	227	<1	32	393	4	0.72	<5	<5	<10	344	1369	2	26	<10	11	10
197270	1361351	<0.005	2	8.65	5	452	2	4	2.05	<4	4	27	<1	1.20	<0.01	55	0.53	177	<1	31	315	4	0.65	<5	<5	<10	340	1455	5	25	<10	8	10

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

Treasury Metals Inc
Exchange Tower 130 King St Suite 3680
Toronto, On, CAN
M5X 1B1
Ph#: (416) 599-4133
Fax#: (416) 599-4959
Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/09/2012
Date Completed: 07/23/2012
Job #: 201242636
Reference: TL 12 266
Sample #: 310

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
197271	1361352	0.006	1	6.98	3	470	3	2	2.11	<4	4	25	<1	1.18	<0.01	47	0.49	199	<1	31	300	6	0.46	<5	<5	<10	331	1403	<2	23	<10	7	8
197272	1361353	<0.005	3	7.02	4	442	3	4	2.18	<4	3	24	<1	1.25	<0.01	50	0.52	211	<1	29	302	9	0.63	<5	<5	<10	338	1381	4	23	<10	8	14
197273	1361354	<0.005	1	7.36	<2	569	2	3	1.96	<4	3	29	<1	1.26	0.04	64	0.53	192	<1	37	304	10	0.70	<5	<5	<10	392	1409	5	25	<10	8	12
197274	1361355	0.005	4	8.52	6	2294	5	<1	4.57	4	19	21	16	4.20	<0.01	139	1.34	830	<1	43	2137	28	0.86	<5	<5	<10	1968	4752	2	112	<10	47	83
197275	1361356	0.007	<1	7.94	6	811	8	<1	2.51	<4	8	24	2	1.75	0.05	106	0.74	306	<1	32	516	10	0.43	<5	<5	<10	590	1990	7	35	<10	13	23
197276	1361357	0.017	<1	8.04	<2	607	4	<1	2.46	<4	5	94	<1	1.50	<0.01	96	0.63	267	<1	52	324	12	0.53	<5	6	<10	344	1484	9	26	<10	8	13
197277	1361358	<0.005	2	7.26	6	502	<2	1	2.41	<4	5	31	<1	1.42	<0.01	56	0.65	297	<1	31	300	3	0.39	<5	<5	<10	322	1361	4	24	<10	8	17
197278D	1361358	<0.005	2	7.00	<2	495	<2	3	2.39	<4	5	23	<1	1.41	<0.01	54	0.64	297	<1	28	296	8	0.42	<5	<5	<10	324	1400	4	24	<10	8	15
197279	1361359	<0.005	1	5.45	<2	336	<2	3	1.91	<4	4	47	<1	1.43	<0.01	37	0.59	272	<1	69	305	5	0.46	<5	<5	<10	268	1156	3	22	<10	8	17
197280	1361360	0.250	1	2.20	397	>5000	<2	5	0.96	<4	6	27	32	2.89	<0.01	13	0.34	<100	<1	21	117	18	0.89	15	<5	<10	151	999	7	16	40	11	13
197281	1361361	0.007	2	6.35	22	1001	<2	<1	2.02	<4	5	40	2	1.54	<0.01	37	0.58	257	<1	56	333	9	0.55	<5	5	<10	282	1367	4	26	<10	9	17
197282	1361362	<0.005	3	7.64	2	384	<2	<1	2.29	<4	5	50	<1	1.26	<0.01	38	0.56	226	<1	45	345	8	0.64	<5	<5	<10	297	1307	2	27	<10	8	15
197283	1361363	0.014	1	8.11	3	544	<2	2	2.01	<4	7	41	<1	1.46	<0.01	41	0.56	241	<1	58	470	8	0.87	<5	<5	<10	307	1304	8	26	<10	9	38
197284	1361364	0.006	<1	7.06	<2	710	<2	<1	1.07	<4	3	49	<1	1.15	0.06	67	0.56	251	<1	62	322	21	0.56	<5	<5	<10	368	954	3	21	<10	7	33
197285	1361365	<0.005	4	7.43	2	868	<2	2	2.65	<4	4	35	10	1.81	<0.01	52	1.09	579	<1	45	316	26	1.12	<5	<5	<10	361	751	2	23	<10	9	38
197286	1361366	0.006	4	7.11	2	874	<2	2	2.66	<4	4	38	13	1.80	<0.01	47	1.10	568	<1	54	306	28	0.88	<5	<5	<10	368	712	8	24	<10	9	57
197287	1361367	0.009	3	5.61	<2	721	<2	<1	0.98	<4	4	26	7	1.45	<0.01	38	0.72	320	<1	40	299	19	0.67	5	<5	<10	227	893	2	24	<10	8	28
197288	1361368	0.010	1	6.26	<2	670	<2	<1	1.34	<4	5	33	<1	1.58	<0.01	45	0.73	343	<1	44	321	16	0.44	<5	<5	<10	220	1301	<2	26	<10	8	27
197289D	1361368	0.006	2	4.37	4	626	<2	3	0.87	<4	5	33	<1	1.51	<0.01	40	0.68	323	<1	44	298	17	0.38	<5	<5	<10	164	1219	6	25	<10	7	28
197290	1361369	0.006	2	5.42	<2	528	<2	<1	1.23	<4	6	41	<1	1.62	<0.01	40	0.67	250	<1	65	298	9	0.40	<5	<5	<10	188	1261	<2	25	<10	7	18

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/09/2012
 Date Completed: 07/23/2012
 Job #: 201242636
 Reference: TL 12 266
 Sample #: 310

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
197291	1361370	0.005	2	3.72	3	432	<2	<1	0.82	<4	4	34	<1	1.35	<0.01	32	0.63	229	<1	54	299	3	0.34	<5	<5	<10	158	992	6	22	<10	7	17
197292	1361371	0.008	1	3.35	<2	472	<2	2	0.77	<4	6	39	<1	1.54	<0.01	33	0.68	267	<1	65	295	8	0.42	<5	<5	<10	137	1014	2	23	<10	6	16
197293	1361372	0.006	2	5.77	3	593	<2	3	1.08	<4	4	45	<1	1.53	<0.01	37	0.72	289	<1	74	311	12	0.51	<5	<5	<10	203	1173	4	26	<10	7	23
197294	1361373	0.006	4	7.34	7	885	<2	<1	1.77	<4	6	37	<1	1.56	<0.01	41	0.93	361	<1	50	324	18	0.63	<5	<5	<10	307	982	7	26	<10	8	63
197295	1361374	0.008	3	7.11	2	1572	<2	<1	2.02	<4	4	55	<1	1.52	<0.01	40	0.94	395	<1	62	294	21	0.83	<5	<5	<10	321	905	<2	25	<10	9	214
197296	1361375	0.014	3	5.53	7	1320	<2	<1	1.28	<4	5	38	7	1.21	<0.01	30	0.71	262	<1	49	292	20	0.56	<5	<5	<10	349	838	2	23	<10	7	207
197297	1361376	0.011	2	4.50	4	1045	<2	6	1.57	<4	4	30	4	1.19	<0.01	31	0.78	340	<1	30	282	17	0.60	<5	<5	<10	307	727	2	21	<10	7	156
197298	1361377	0.009	2	5.51	2	1152	<2	5	1.86	<4	4	40	1	1.51	<0.01	35	0.87	317	<1	54	320	17	0.44	<5	<5	<10	313	1121	7	26	<10	7	57
197299	1361378	0.005	2	5.82	4	693	<2	<1	2.23	<4	4	34	<1	1.35	<0.01	34	0.85	272	<1	39	291	15	0.44	<5	<5	<10	318	1085	<2	24	<10	7	37
197300R	1361378	0.015	1	4.87	<2	646	<2	3	2.06	<4	3	27	<1	1.28	<0.01	31	0.78	260	<1	33	288	15	0.35	<5	<5	<10	297	1037	3	24	<10	6	28
197301	1361379	0.012	3	5.96	12	618	<2	<1	1.80	<4	6	41	3	1.41	<0.01	31	0.88	291	<1	55	381	18	0.93	<5	<5	<10	237	959	2	27	<10	6	39
197302	1361380	0.015	1	4.21	6	382	<2	<1	2.18	<4	16	55	23	3.34	<0.01	11	1.35	668	<1	37	625	6	0.38	<5	<5	<10	265	2633	6	109	17	19	54
197303	1361381	0.017	1	5.59	13	464	<2	4	1.25	<4	7	30	3	1.40	<0.01	31	0.96	325	<1	37	434	27	0.82	<5	<5	<10	169	1354	7	35	<10	7	35
197304	1361382	0.030	3	4.87	5	575	<2	3	1.24	<4	10	36	35	1.59	<0.01	33	0.97	450	<1	50	407	64	0.62	<5	<5	<10	137	1452	<2	29	<10	5	270
197305	1361383	0.047	3	4.43	2	413	<2	<1	1.17	<4	8	37	47	1.36	<0.01	29	0.86	389	<1	47	434	98	0.64	<5	<5	<10	126	1319	5	27	<10	5	559
197306	1361384	<0.005	1	5.16	<2	417	<2	<1	1.57	<4	5	45	10	1.70	<0.01	34	1.08	364	<1	59	442	44	0.40	<5	<5	<10	159	1461	<2	31	<10	5	83
197307	1361385	<0.005	1	6.02	<2	425	<2	<1	1.90	<4	7	43	11	1.68	<0.01	40	1.12	349	<1	51	414	19	0.38	<5	<5	<10	186	1629	3	31	<10	6	41
197308	1361386	<0.005	2	4.85	6	403	<2	<1	1.68	<4	7	42	11	1.58	<0.01	34	1.01	325	<1	60	391	13	0.44	<5	<5	<10	173	1473	8	28	<10	6	41
197309	1361387	<0.005	<1	6.34	<2	706	<2	<1	1.72	<4	6	31	12	1.28	<0.01	37	0.95	235	<1	39	427	11	0.42	<5	<5	<10	238	1647	4	30	<10	6	32
197310	1361388	<0.005	2	5.80	6	913	<2	<1	1.98	<4	6	39	14	1.39	<0.01	40	0.96	243	<1	51	417	14	0.42	<5	<5	<10	282	1882	6	31	<10	6	18

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/09/2012
 Date Completed: 07/23/2012
 Job #: 201242636
 Reference: TL 12 266
 Sample #: 310

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
197311D	1361388	<0.005	3	5.76	5	911	<2	<1	1.95	<4	6	38	13	1.37	<0.01	40	0.92	237	<1	50	415	10	0.43	<5	<5	<10	280	1862	5	31	<10	6	16

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 14, 2012

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/30/2012
 Date Completed: 08/14/2012
 Job #: 201242857
 Reference: TL12267
 Sample #: 109

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
217648	1365606	953	0.028	0.953
217649	1365607	405	0.012	0.405
217650	1365608	1793	0.052	1.793
217651	1365609	770	0.022	0.770
217652	1365610	<5	<0.001	<0.005
217653	1365611	49	0.001	0.049
217654	1365612	9	<0.001	0.009
217655	1365613	20	<0.001	0.020
217656	1365614	11	<0.001	0.011
217657	1365615	15	<0.001	0.015
217658 Dup	1365615	13	<0.001	0.013
217659	1365616	12	<0.001	0.012
217660	1365617	10	<0.001	0.010
217661	1365618	12	<0.001	0.012
217662	1365619	7	<0.001	0.007
217663	1365620	5092	0.149	5.092
217664	1365621	10	<0.001	0.010
217665	1365622	21	<0.001	0.021
217666	1365623	53	0.002	0.053
217667	1365624	30	<0.001	0.030
217668	1365625	172	0.005	0.172
217669 Dup	1365625	188	0.005	0.188
217670	1365626	16	<0.001	0.016
217671	1365627	25	<0.001	0.025
217672	1365628	25	<0.001	0.025
217673	1365629	24	<0.001	0.024
217674	1365630	9	<0.001	0.009
217675	1365631	31	<0.001	0.031
217676	1365632	45	0.001	0.045
217677	1365633	45	0.001	0.045

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 14, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/30/2012
 Date Completed: 08/14/2012
 Job #: 201242857
 Reference: TL12267
 Sample #: 109

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
217678	1365634	100	0.003	0.100
217679	1365635	47	0.001	0.047
217680 Dup	1365635	38	0.001	0.038
217681	1365636	36	0.001	0.036
217682	1365637	52	0.002	0.052
217683	1365638	5437	0.159	5.437
217684	1365639	126	0.004	0.126
217685	1365640	1938	0.057	1.938
217686	1365641	152	0.004	0.152
217687	1365642	960	0.028	0.960
217688	1365643	114	0.003	0.114
217689	1365644	20	<0.001	0.020
217690	1365645	50	0.001	0.050
217691 Dup	1365645	51	0.001	0.051
217692	1365646	18	<0.001	0.018
217693	1365647	22	<0.001	0.022
217694	1365648	16	<0.001	0.016
217695	1365649	18	<0.001	0.018
217696	1365650	6	<0.001	0.006
217697	1365651	18	<0.001	0.018
217698	1365652	56	0.002	0.056
217699	1365653	119	0.003	0.119
217700	1365654	46	0.001	0.046
217701	1365655	161	0.005	0.161
217702 Dup	1365655	224	0.007	0.224
217703	1365656	224	0.007	0.224
217704	1365657	57	0.002	0.057
217705	1365658	<5	<0.001	<0.005
217706	1365659	13	<0.001	0.013
217707	1365660	222	0.006	0.222

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 14, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/30/2012
 Date Completed: 08/14/2012
 Job #: 201242857
 Reference: TL12267
 Sample #: 109

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
217708	1365661	27	<0.001	0.027
217709	1365662	47	0.001	0.047
217710	1365663	11	<0.001	0.011
217711	1365664	167	0.005	0.167
217712	1365665	648	0.019	0.648
217713 Rep	1365665	380	0.011	0.380
217714	1365666	107	0.003	0.107
217715	1365667	1910	0.056	1.910
217716	1365668	25	<0.001	0.025
217717	1365669	15	<0.001	0.015
217718	1365670	<5	<0.001	<0.005
217719	1365671	47	0.001	0.047
217720	1365672	193	0.006	0.193
217721	1365673	128	0.004	0.128
217722	1365674	1264	0.037	1.264
217723	1365675	1097	0.032	1.097
217724 Dup	1365675	1135	0.033	1.135
217725	1365676	1694	0.049	1.694
217726	1365677	207	0.006	0.207
217727	1365678	270	0.008	0.270
217728	1365679	178	0.005	0.178
217729	1365680	5059	0.148	5.059
217730	1365681	320	0.009	0.320
217731	1365682	38	0.001	0.038
217732	1365683	123	0.004	0.123
217733	1365684	26	<0.001	0.026
217734	1365685	100	0.003	0.100
217735 Dup	1365685	55	0.002	0.055
217736	1365686	107	0.003	0.107
217737	1365687	51	0.001	0.051

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 14, 2012

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/30/2012
 Date Completed: 08/14/2012
 Job #: 201242857
 Reference: TL12267
 Sample #: 109

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
217738	1365688	68	0.002	0.068
217739	1365689	161	0.005	0.161
217740	1365690	<5	<0.001	<0.005
217741	1365691	8150	0.238	8.150
217742	1365692	241	0.007	0.241
217743	1365693	778	0.023	0.778
217744	1365694	433	0.013	0.433
217745	1365695	131	0.004	0.131
217746 Dup	1365695	108	0.003	0.108
217747	1365696	92	0.003	0.092
217748	1365697	508	0.015	0.508
217749	1365698	1057	0.031	1.057
217750	1365699	24	<0.001	0.024
217751	1365700	1970	0.057	1.970
217752	1365701	438	0.013	0.438
217753	1365702	126	0.004	0.126
217754	1365703	35	0.001	0.035
217755	1365704	7	<0.001	0.007
217756	1365705	7	<0.001	0.007
217757 Dup	1365705	10	<0.001	0.010
217758	1365706	11	<0.001	0.011
217759	1365707	8	<0.001	0.008
217760	1365708	7	<0.001	0.007
217761	1365709	<5	<0.001	<0.005
217762	1365710	269	0.008	0.269
217763	1365711	10	<0.001	0.010
217764	1365712	18	<0.001	0.018
217765	1365713	13	<0.001	0.013
217766	1365714	18	<0.001	0.018

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AlSu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, October 25, 2012

Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 09/21/2012
 Date Completed: 10/05/2012
 Job #: 201243721
 Reference: TL 12 268
 Sample #: 42

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
273396	1365915	0.017	1	4.58	26	519	<2	23	1.67	<4	9	28	37	2.16	0.07	13	1.03	561	<1	53	630	35	0.95	<5	19	<10	152	1723	<2	39	<10	6	65
273397	1365916	0.035	1	4.85	22	556	<2	17	1.66	<4	8	31	19	2.12	0.21	13	0.99	547	<1	60	617	37	0.98	<5	21	<10	155	1744	6	38	<10	6	61
273398	1365917	0.047	2	3.70	28	447	<2	22	1.07	<4	8	28	21	1.73	0.15	8	0.76	511	<1	48	526	31	1.17	<5	15	<10	125	1501	<2	31	<10	6	82
273399	1365918	0.021	<1	3.75	23	351	<2	19	1.63	<4	7	31	12	1.65	0.16	4	0.96	407	<1	51	570	20	0.82	<5	18	<10	159	1448	<2	30	<10	6	55
273400	1365919	0.020	1	5.03	42	376	<2	22	2.41	4	10	51	18	2.31	0.18	4	1.23	678	<1	68	541	19	1.59	<5	21	<10	145	1451	<2	36	<10	7	64
273401	1365920	4.889	64	2.50	46	415	<2	20	1.05	22	13	31	52	2.71	0.26	<1	0.76	481	<1	28	521	548	0.69	42	15	218	176	1702	<2	77	50	12	1758
273402	1365921	0.023	1	5.26	29	372	<2	19	2.23	<4	7	30	12	1.74	0.53	3	1.18	555	<1	57	493	20	0.85	<5	9	<10	83	1504	<2	29	<10	6	51
273403	1365922	0.037	<1	3.45	48	228	<2	36	1.48	<4	7	20	12	1.58	0.24	<1	0.80	405	<1	42	487	18	1.18	<5	16	<10	69	1196	2	22	<10	5	61
273404	1365923	0.039	<1	4.56	61	296	<2	<1	1.31	<4	7	23	18	1.57	0.27	<1	0.74	427	<1	48	495	21	1.36	<5	17	<10	71	1325	<2	27	<10	6	57
273405	1365924	0.091	<1	4.46	36	236	<2	21	1.20	4	19	108	37	3.13	0.33	4	1.14	494	<1	85	446	20	1.32	<5	16	11	88	1917	<2	63	<10	12	51
273406D	1365924	0.131	<1	4.37	32	204	<2	13	1.48	4	22	122	49	3.83	0.28	5	1.39	592	<1	105	533	25	1.44	<5	13	<10	104	2061	<2	65	<10	14	68
273407	1365925	0.043	1	4.30	22	207	<2	23	1.27	4	21	130	56	3.67	0.25	3	1.14	567	<1	123	509	35	1.64	<5	17	<10	85	1759	<2	65	<10	14	72
273408	1365926	0.608	1	4.93	24	225	2	17	1.45	4	19	115	46	3.79	0.23	5	1.35	740	<1	98	477	35	1.69	<5	14	<10	73	2004	<2	67	<10	15	95
273409	1365927	0.088	<1	3.97	17	197	<2	10	1.53	5	21	121	51	3.88	0.17	6	1.46	847	<1	90	491	23	1.22	<5	12	<10	68	2133	<2	66	<10	14	81
273410	1365928	1.439	1	3.05	38	246	<2	17	1.50	4	14	63	45	2.39	0.18	<1	1.05	788	<1	82	474	179	1.29	<5	20	<10	60	1354	<2	39	<10	9	322
273411	1365929	0.089	<1	4.85	31	400	2	16	2.01	4	9	32	13	1.67	0.19	3	1.15	873	<1	56	471	67	0.86	<5	24	11	71	1368	<2	29	<10	6	241
273412	1365930	0.012	<1	1.64	17	270	<2	20	1.59	4	14	44	22	3.00	<0.01	<1	1.17	601	<1	32	571	5	0.25	<5	16	10	154	2200	<2	98	15	13	56
273413	1365931	0.237	3	2.52	44	266	<2	15	1.15	<4	7	23	28	1.62	0.17	<1	0.75	634	<1	43	470	349	1.19	<5	16	<10	62	1203	<2	24	<10	5	332
273414	1365932	0.491	1	1.76	77	143	<2	11	0.85	4	16	80	45	2.75	0.15	<1	0.71	485	<1	89	471	196	2.40	<5	13	<10	55	1124	<2	37	<10	10	193
273415	1365933	0.166	<1	2.45	26	145	<2	20	0.66	4	21	101	59	3.64	0.24	<1	1.10	601	<1	105	519	39	1.84	<5	13	<10	51	1540	<2	57	<10	14	105

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, October 25, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 09/21/2012
 Date Completed: 10/05/2012
 Job #: 201243721
 Reference: TL 12 268
 Sample #: 42

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
273416	1365934	0.177	<1	3.11	37	152	<2	8	1.06	4	19	111	53	3.06	0.28	2	1.02	504	<1	102	528	45	1.31	<5	16	<10	67	1654	<2	55	<10	14	65
273417D	1365934	0.128	<1	2.58	32	125	<2	21	1.01	4	19	100	49	2.84	0.23	<1	0.96	474	<1	95	504	44	1.22	<5	16	<10	64	1516	<2	49	<10	13	61
273418	1365935	0.710	2	1.88	52	113	<2	27	0.79	8	19	94	70	3.13	0.20	<1	0.92	470	<1	103	469	302	1.73	<5	19	<10	65	1555	<2	43	12	12	1243
273419	1365936	0.370	2	1.92	53	123	<2	19	0.80	8	20	98	58	3.16	0.18	<1	0.95	477	<1	103	512	371	1.69	<5	17	<10	65	1557	<2	44	11	13	1328
273420	1365937	0.193	<1	2.72	35	210	<2	12	1.47	4	17	122	44	2.87	0.22	<1	1.06	567	<1	100	469	54	1.22	<5	19	<10	84	1799	3	50	<10	13	140
273421	1365938	0.243	2	2.99	80	369	<2	15	0.34	4	13	71	45	2.53	0.22	<1	0.42	218	<1	83	447	172	2.29	<5	17	<10	65	1605	<2	44	<10	9	354
273422	1365939	0.397	<1	2.37	24	362	<2	20	0.32	<4	5	38	17	1.28	0.21	<1	0.38	176	<1	63	450	31	0.84	6	16	<10	53	1103	<2	23	<10	5	40
273423	1365940	2.133	<1	1.40	19	273	<2	18	1.54	5	16	46	34	3.38	<0.01	1	1.24	643	<1	37	606	9	0.24	<5	13	<10	141	2242	<2	104	13	13	51
273424	1365941	0.014	<1	3.32	20	317	<2	18	1.76	<4	6	26	14	1.51	0.33	<1	1.06	563	<1	48	439	27	0.69	<5	20	<10	85	1180	9	24	<10	5	62
273425	1365942	0.014	<1	3.46	15	328	<2	38	1.64	<4	6	29	16	1.65	0.33	<1	1.01	473	<1	55	440	16	0.88	<5	15	<10	86	1242	<2	25	<10	5	87
273426	1365943	0.023	<1	2.87	32	74	2	15	5.17	<4	5	19	31	1.96	<0.01	<1	2.36	872	<1	37	536	12	0.76	<5	19	<10	124	1228	7	24	310	5	96
273427	1365944	0.014	<1	0.86	17	182	<2	20	0.95	<4	3	73	13	1.01	0.28	<1	0.64	264	<1	112	300	10	0.40	<5	22	<10	57	704	<2	16	20	3	44
273428D	1365944	0.017	<1	0.47	14	170	<2	22	0.76	<4	3	70	12	0.93	0.21	<1	0.57	237	<1	103	296	6	0.35	<5	17	<10	54	657	<2	15	<10	3	38
273429	1365945	0.008	<1	4.27	20	398	<2	7	2.70	<4	6	31	20	1.75	0.27	3	1.54	642	<1	51	530	20	0.47	<5	21	<10	111	1414	6	27	<10	5	69
273430	1365946	0.024	<1	2.66	17	298	<2	37	1.77	<4	6	25	72	1.64	0.27	<1	1.04	449	<1	51	469	21	0.75	<5	16	<10	80	1124	<2	21	<10	5	188
273431	1365947	0.017	<1	4.99	17	330	2	39	4.01	5	7	29	51	2.45	0.31	1	2.43	1156	<1	48	482	34	1.06	6	18	11	111	1506	14	34	<10	7	305
273432	1365948	0.019	<1	5.40	17	281	3	20	2.85	4	7	23	49	2.08	0.35	15	2.00	739	<1	34	475	16	1.10	<5	19	<10	118	1543	9	31	<10	8	394
273433	1365949	0.017	<1	5.93	16	536	<2	24	1.89	<4	6	22	35	1.61	0.19	9	1.13	479	<1	30	499	23	0.98	<5	14	<10	99	1666	2	34	<10	6	51
273434	1365950	0.007	<1	4.59	17	415	<2	25	2.12	4	15	49	26	3.32	0.21	3	1.27	665	<1	34	613	4	0.42	<5	12	<10	254	2774	<2	114	22	16	51
273435	1365951	0.104	2	4.47	22	367	2	22	2.60	10	6	27	114	2.15	0.30	1	1.38	541	<1	37	332	21	1.40	<5	15	11	103	1433	<2	32	80	7	1884

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, October 25, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 09/21/2012
 Date Completed: 10/05/2012
 Job #: 201243721
 Reference: TL 12 268
 Sample #: 42

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
273436	1365952	0.059	1	4.50	23	460	<2	20	0.79	<4	8	24	61	1.66	0.25	6	0.65	284	<1	33	457	15	1.31	<5	21	11	78	1645	<2	33	13	6	168
273437	1365953	0.023	<1	3.73	18	400	<2	10	1.70	4	7	19	44	1.86	0.32	4	0.99	387	<1	26	489	17	0.70	<5	20	<10	110	1526	<2	30	<10	5	206
273438	1365954	0.007	<1	4.92	12	501	<2	19	1.82	<4	7	17	9	1.66	0.33	7	0.92	339	<1	31	517	6	0.53	<5	18	<10	120	1742	<2	32	<10	6	61
273439D	1365954	0.008	<1	5.43	17	537	<2	13	1.94	<4	7	18	8	1.69	0.31	8	0.94	344	<1	27	543	5	0.56	<5	16	<10	127	1791	2	32	<10	6	70
273440	1365955	0.009	<1	5.08	17	478	<2	14	2.48	<4	7	13	10	1.81	0.26	7	1.22	378	<1	25	504	10	0.49	<5	18	<10	132	1650	<2	31	<10	5	52
273441	1365956	0.011	<1	4.95	14	439	<2	13	2.53	<4	7	14	10	1.82	0.44	7	1.22	374	<1	35	492	9	0.50	<5	18	<10	133	1675	4	31	<10	5	51

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Friday, October 5, 2012

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 09/21/2012
 Date Completed: 10/05/2012
 Job #: 201243721
 Reference: TL 12 268
 Sample #: 42

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
273396	1365915	17	<0.001	0.017
273397	1365916	35	0.001	0.035
273398	1365917	47	0.001	0.047
273399	1365918	21	<0.001	0.021
273400	1365919	20	<0.001	0.020
273401	1365920	4889	0.143	4.889
273402	1365921	23	<0.001	0.023
273403	1365922	37	0.001	0.037
273404	1365923	39	0.001	0.039
273405	1365924	91	0.003	0.091
273406 Dup	1365924	131	0.004	0.131
273407	1365925	43	0.001	0.043
273408	1365926	608	0.018	0.608
273409	1365927	88	0.003	0.088
273410	1365928	1439	0.042	1.439
273411	1365929	89	0.003	0.089
273412	1365930	12	<0.001	0.012
273413	1365931	237	0.007	0.237
273414	1365932	491	0.014	0.491
273415	1365933	166	0.005	0.166
273416	1365934	177	0.005	0.177
273417 Dup	1365934	128	0.004	0.128
273418	1365935	710	0.021	0.710
273419	1365936	370	0.011	0.370
273420	1365937	193	0.006	0.193
273421	1365938	243	0.007	0.243
273422	1365939	397	0.012	0.397
273423	1365940	2133	0.062	2.133
273424	1365941	14	<0.001	0.014
273425	1365942	14	<0.001	0.014

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Friday, October 5, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 09/21/2012
 Date Completed: 10/05/2012
 Job #: 201243721
 Reference: TL 12 268
 Sample #: 42

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
273426	1365943	23	<0.001	0.023
273427	1365944	14	<0.001	0.014
273428 Dup	1365944	17	<0.001	0.017
273429	1365945	8	<0.001	0.008
273430	1365946	24	<0.001	0.024
273431	1365947	17	<0.001	0.017
273432	1365948	19	<0.001	0.019
273433	1365949	17	<0.001	0.017
273434	1365950	7	<0.001	0.007
273435	1365951	104	0.003	0.104
273436	1365952	59	0.002	0.059
273437	1365953	23	<0.001	0.023
273438	1365954	7	<0.001	0.007
273439 Dup	1365954	8	<0.001	0.008
273440	1365955	9	<0.001	0.009
273441	1365956	11	<0.001	0.011

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/20/2012
 Date Completed: 08/07/2012
 Job #: 201242758
 Reference: TL12269
 Sample #: 82

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
205804	1365432	0.013	2	5.18	23	454	<2	<1	1.17	<4	5	29	14	1.58	0.13	11	1.06	565	<1	67	531	25	1.24	<5	6	<10	125	1796	<2	40	<10	6	38
205805	1365433	0.091	4	2.89	25	426	<2	<1	0.08	<4	3	29	11	0.87	0.07	3	0.61	279	<1	70	436	64	0.81	<5	6	<10	64	1269	2	26	<10	4	73
205806	1365434	0.115	4	6.95	18	557	<2	<1	0.20	<4	4	40	11	0.66	0.10	12	0.64	208	1	74	350	168	0.71	6	9	<10	104	1440	2	32	11	6	133
205807	1365435	0.649	4	4.84	20	356	<2	<1	<0.01	<4	1	31	12	0.64	0.13	5	0.37	<100	<1	65	387	172	0.79	6	7	<10	77	1101	2	24	<10	5	83
205808	1365436	0.702	3	3.28	19	320	2	<1	<0.01	<4	4	26	10	0.66	0.08	1	0.32	<100	<1	56	307	120	0.77	<5	7	<10	64	1015	<2	23	<10	4	119
205809	1365437	2.664	13	5.44	54	363	<2	<1	<0.01	7	4	43	95	1.59	0.09	10	0.43	<100	<1	85	291	1492	1.96	9	13	<10	82	1273	<2	29	21	5	1847
205810	1365438	0.070	2	3.64	26	381	<2	<1	0.45	<4	4	39	8	1.10	0.13	7	0.73	392	<1	76	396	39	0.89	<5	8	<10	108	1296	<2	29	<10	5	50
205811	1365439	0.051	4	5.82	23	362	<2	5	1.54	<4	3	24	9	1.18	0.18	15	1.30	970	<1	56	386	48	1.11	<5	8	<10	145	1262	4	26	<10	5	47
205812	1365440	5.009	66	3.34	46	487	<2	<1	1.26	23	15	36	52	3.25	0.14	5	0.91	509	<1	47	567	655	0.64	56	8	263	249	1994	<2	94	62	14	1901
205813	1365441	0.064	5	5.45	30	408	2	<1	0.44	<4	4	30	21	1.14	0.12	18	0.68	264	<1	60	371	58	1.30	<5	<5	<10	142	1348	2	27	<10	6	45
205814D	1365441	0.061	5	4.33	28	373	2	<1	0.31	<4	4	28	22	1.13	0.17	15	0.64	253	<1	61	372	48	1.27	<5	<5	<10	123	1256	<2	26	<10	5	43
205815	1365442	0.009	2	5.45	18	302	2	<1	1.87	<4	7	22	8	1.91	0.16	17	0.96	171	<1	57	396	21	2.27	<5	12	<10	321	1020	<2	31	<10	6	76
205816	1365443	0.007	1	4.80	14	342	<2	<1	1.52	<4	4	24	5	1.80	0.13	10	0.97	113	<1	57	448	18	2.07	<5	7	<10	280	1007	3	33	<10	6	45
205817	1365444	0.008	1	4.48	12	274	<2	<1	1.86	<4	5	25	4	1.60	0.10	11	1.26	165	<1	55	450	15	1.56	<5	12	<10	276	1279	3	42	<10	6	38
205818	1365445	0.010	2	4.94	13	333	2	<1	1.47	<4	5	27	7	1.31	0.06	13	0.95	127	<1	49	457	19	1.33	<5	11	<10	306	816	<2	32	<10	6	21
205819	1365446	0.008	2	5.04	12	435	<2	<1	2.03	<4	11	34	8	1.36	0.07	16	1.31	161	<1	82	514	16	0.92	5	8	<10	365	1063	<2	33	<10	5	28
205820	1365447	0.008	1	5.08	17	474	<2	<1	1.83	<4	9	33	8	1.56	0.08	16	1.25	213	<1	72	488	17	1.58	<5	11	<10	295	1631	12	42	<10	6	55
205821	1365448	0.008	1	3.75	24	427	<2	<1	1.11	<4	11	44	6	1.93	0.02	17	1.11	208	<1	72	396	20	2.15	<5	10	<10	203	1491	3	35	<10	6	72
205822	1365449	0.015	2	4.43	24	416	<2	<1	0.74	<4	23	42	32	1.89	0.12	23	0.82	177	<1	88	431	20	2.25	<5	<5	<10	191	1591	2	33	<10	6	253
205823	1365450	<0.005	<1	4.58	12	415	<2	<1	2.37	4	17	53	23	3.46	0.21	8	1.43	682	<1	54	615	10	0.32	<5	16	<10	298	2927	14	119	24	17	51

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/20/2012
 Date Completed: 08/07/2012
 Job #: 201242758
 Reference: TL12269
 Sample #: 82

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
205824	1365451	0.018	2	5.04	27	380	<2	<1	0.37	<4	13	43	8	1.37	0.19	14	0.58	125	<1	75	419	26	1.70	<5	10	<10	151	1347	<2	35	<10	7	26
205825D	1365451	0.009	2	2.80	23	323	<2	<1	0.17	<4	11	42	7	1.31	0.17	8	0.51	117	<1	67	406	20	1.56	<5	<5	<10	116	1177	<2	31	<10	6	25
205826	1365452	0.011	1	3.77	19	387	<2	<1	0.44	<4	10	27	34	1.47	0.18	10	0.50	178	<1	59	573	19	1.47	<5	<5	<10	187	1404	<2	36	<10	6	16
205827	1365453	0.011	2	4.51	21	428	<2	<1	1.23	<4	11	19	11	1.24	0.18	22	1.05	340	<1	56	618	12	0.83	5	<5	<10	292	1648	6	37	<10	7	32
205828	1365454	0.010	2	7.41	19	590	2	<1	2.14	<4	10	16	7	1.63	0.12	27	1.36	437	<1	52	620	15	1.38	<5	16	<10	413	1664	2	40	<10	8	25
205829	1365455	0.016	2	5.83	20	598	<2	<1	0.68	<4	8	20	7	1.89	0.11	13	0.62	295	<1	56	593	13	2.01	<5	13	<10	287	1135	<2	37	<10	7	48
205830	1365456	0.011	1	4.64	24	579	<2	<1	0.52	<4	9	23	8	1.91	0.05	10	0.59	288	<1	62	599	13	1.94	<5	9	<10	266	1063	5	36	<10	6	50
205831	1365457	0.012	2	5.68	21	582	<2	<1	0.78	<4	8	14	7	1.91	0.04	13	0.59	265	<1	46	641	14	1.95	<5	13	<10	272	1186	3	38	<10	7	38
205832	1365458	0.011	2	5.53	34	538	2	<1	1.86	<4	9	27	9	1.96	0.09	14	0.98	1048	<1	54	557	29	1.70	<5	11	<10	284	1512	9	35	<10	7	53
205833	1365459	0.015	3	5.72	40	586	2	<1	2.05	<4	10	38	19	1.96	0.13	13	0.70	630	<1	71	561	34	2.07	<5	<5	<10	244	1765	4	41	<10	7	70
205834	1365460	2.018	1	3.92	21	432	<2	<1	2.22	5	19	56	33	3.86	0.16	7	1.47	720	<1	57	647	15	0.27	<5	6	<10	273	2789	<2	125	21	17	67
205835	1365461	0.025	4	5.96	42	519	2	<1	2.19	<4	9	30	15	2.20	0.16	17	0.73	584	<1	64	573	43	2.55	<5	11	<10	209	1780	<2	36	<10	7	77
205836D	1365461	0.030	3	4.91	38	476	<2	<1	2.11	<4	10	32	16	2.19	0.17	13	0.69	569	<1	70	570	41	2.44	<5	5	<10	202	1669	2	35	<10	7	75
205837	1365462	0.027	4	4.82	36	511	<2	<1	1.67	<4	8	28	18	2.03	0.25	11	0.90	526	<1	60	563	27	2.03	<5	7	<10	205	1651	2	33	<10	6	40
205838	1365463	0.102	20	4.84	33	474	<2	<1	0.99	<4	9	28	52	1.91	0.16	9	0.63	396	<1	61	586	46	2.01	<5	8	<10	176	1722	3	38	<10	7	219
205839	1365464	0.032	6	5.05	24	457	<2	<1	2.17	<4	8	24	33	2.04	0.18	14	1.20	913	<1	61	662	36	1.37	<5	7	<10	221	1517	<2	35	<10	7	103
205840	1365465	0.068	20	5.59	33	556	<2	<1	<0.01	<4	7	30	53	1.45	0.06	4	0.30	<100	<1	72	627	62	1.60	7	11	<10	142	1695	<2	36	<10	7	395
205841	1365466	0.064	7	5.77	27	528	<2	<1	1.34	<4	7	24	11	1.92	0.08	16	0.87	566	<1	54	597	51	1.41	<5	6	<10	239	1684	<2	39	<10	7	135
205842	1365467	0.182	11	5.86	31	473	<2	<1	1.12	<4	9	30	7	1.65	0.05	15	0.72	375	<1	77	590	58	0.98	<5	10	<10	216	1968	2	40	<10	7	120
205843	1365468	0.115	3	6.58	38	565	<2	<1	1.08	<4	11	24	5	1.53	0.08	19	0.70	354	<1	65	636	30	1.02	<5	7	<10	223	2056	2	40	<10	8	47

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By:  Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012

Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/20/2012
 Date Completed: 08/07/2012
 Job #: 201242758
 Reference: TL12269
 Sample #: 82

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
205844	1365469	0.072	3	6.33	31	432	2	<1	1.37	<4	10	19	4	1.85	0.07	19	0.86	415	<1	58	619	23	1.27	5	7	<10	224	1999	3	38	<10	8	97
205845	1365470	0.006	<1	4.69	12	410	<2	<1	2.40	5	18	54	23	3.49	0.08	9	1.45	683	<1	52	639	10	0.34	<5	<5	<10	297	2881	3	120	22	17	60
205846	1365471	0.088	4	6.30	40	304	<2	2	1.78	<4	10	29	11	2.17	0.10	12	1.13	540	<1	61	539	38	1.94	5	5	<10	106	1644	2	36	<10	8	82
205847D	1365471	0.079	4	5.79	43	295	<2	<1	1.75	<4	10	37	14	2.21	0.10	11	1.12	549	<1	81	553	34	1.90	<5	7	<10	103	1595	<2	35	<10	8	86
205848	1365472	0.034	3	5.96	33	309	<2	<1	1.63	<4	8	20	14	1.84	0.08	9	1.06	545	<1	51	561	35	1.62	<5	<5	<10	96	1572	<2	34	<10	8	37
205849	1365473	0.011	3	7.05	39	334	2	<1	1.60	<4	10	24	16	1.73	0.14	11	1.09	601	<1	52	579	35	1.32	<5	14	<10	101	1678	<2	39	<10	9	69
205850	1365474	0.022	3	4.39	41	231	<2	<1	1.35	<4	10	22	17	1.50	0.07	4	0.96	574	<1	63	559	38	1.24	<5	<5	<10	95	1011	3	30	<10	7	213
205851	1365475	0.026	2	4.08	39	281	<2	<1	0.23	<4	13	27	13	1.23	0.13	<1	0.41	141	<1	74	540	29	1.27	<5	<5	<10	73	1070	<2	33	<10	6	189
205852	1365476	0.029	3	5.49	42	327	<2	<1	0.28	<4	15	20	13	1.40	0.07	3	0.44	154	<1	59	513	32	1.56	<5	5	<10	82	1237	4	37	<10	7	183
205853	1365477	0.032	3	5.17	27	297	<2	<1	1.10	<4	10	31	28	1.81	0.05	4	0.77	330	<1	66	489	28	1.90	<5	13	<10	114	1214	5	36	<10	7	174
205854	1365478	0.010	2	6.37	22	352	<2	3	2.60	<4	9	48	9	2.14	0.16	13	1.53	615	<1	102	551	29	1.40	<5	7	<10	154	1481	5	39	<10	7	65
205855	1365479	0.030	3	6.01	26	418	<2	<1	2.04	<4	8	32	11	1.87	0.11	10	1.21	464	<1	68	535	39	1.09	5	13	<10	126	1557	3	36	<10	7	48
205856	1365480	0.235	2	1.00	438	>5000	<2	<1	0.91	4	7	19	32	2.99	0.06	4	0.28	<100	6	27	<100	22	0.76	15	6	<10	128	796	4	16	52	9	25
205857	1365481	0.014	2	6.76	57	412	2	<1	2.04	<4	10	52	10	2.24	0.06	12	1.19	525	<1	87	552	38	1.62	<5	6	<10	124	1673	2	42	<10	8	47
205858D	1365481	0.013	3	7.80	58	420	2	<1	2.08	<4	10	51	10	2.18	0.19	16	1.21	509	<1	94	538	40	1.65	<5	6	<10	130	1673	<2	43	<10	9	44
205859	1365482	0.063	3	6.20	74	395	2	<1	1.95	5	20	128	46	3.21	0.07	12	1.24	587	<1	107	587	64	2.36	<5	6	<10	102	1879	<2	73	<10	12	248
205860	1365483	0.470	5	5.23	104	369	2	<1	0.75	5	17	130	121	2.62	0.06	7	0.78	297	<1	105	469	195	2.49	7	5	<10	76	1289	2	69	<10	10	525
205861	1365484	0.767	7	4.15	133	370	2	<1	0.35	6	28	127	219	3.85	0.07	5	0.95	315	<1	123	546	307	2.85	<5	8	<10	55	1302	<2	83	12	10	399
205862	1365485	0.731	23	3.74	134	503	2	<1	<0.01	<4	9	27	266	1.55	0.02	<1	0.28	<100	<1	57	418	394	1.78	32	13	<10	53	951	<2	29	11	5	244
205863	1365486	0.099	2	4.52	45	442	2	<1	0.21	<4	8	41	15	1.25	0.11	4	0.51	137	<1	71	502	48	1.26	<5	14	<10	69	1278	<2	32	11	7	110

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/20/2012
 Date Completed: 08/07/2012
 Job #: 201242758
 Reference: TL12269
 Sample #: 82

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
205864	1365487	0.032	2	6.91	55	447	2	<1	1.68	4	9	41	23	1.99	0.39	13	1.16	500	<1	77	540	45	1.34	<5	<5	<10	107	1814	4	41	12	8	298
205865	1365488	0.070	3	7.75	16	387	2	<1	2.14	4	21	151	41	3.24	0.27	21	1.62	607	<1	92	493	30	1.05	5	9	<10	114	2727	<2	83	<10	17	58
205866	1365489	0.054	3	6.63	26	349	2	<1	1.89	4	20	143	43	3.32	0.16	16	1.54	524	<1	96	499	42	1.33	<5	12	<10	140	2614	<2	79	<10	16	61
205867	1365490	0.008	2	5.17	11	434	<2	<1	2.41	5	17	54	23	3.42	0.30	9	1.44	678	<1	52	615	11	0.36	<5	10	<10	301	2968	<2	118	24	17	50
205868	1365491	0.163	1	3.25	53	273	2	<1	1.45	4	17	113	41	3.00	0.07	4	1.20	452	<1	99	513	41	1.63	<5	8	<10	106	1877	7	57	<10	11	67
205869R	1365491	0.192	3	7.74	49	366	2	<1	1.90	4	19	128	45	3.11	0.16	18	1.40	477	<1	100	555	43	1.87	<5	10	<10	139	2363	<2	70	<10	15	78
205870	1365492	0.491	3	6.27	76	330	2	<1	0.56	<4	18	150	39	2.31	0.22	9	0.66	219	<1	109	477	50	2.13	<5	7	<10	84	1949	<2	70	<10	14	74
205871	1365493	1.018	3	6.73	83	366	2	<1	0.59	5	22	165	56	3.37	0.24	11	0.78	296	1	124	532	103	3.12	<5	<5	<10	87	2153	<2	99	<10	15	172
205872	1365494	0.693	4	8.23	88	351	2	<1	1.08	6	19	172	96	3.39	0.07	18	1.02	347	5	145	470	144	3.10	<5	8	<10	110	1897	3	73	12	16	499
205873	1365495	1.682	6	6.27	65	343	2	<1	0.67	8	18	155	127	2.88	0.03	11	0.72	236	3	140	433	855	2.72	5	7	<10	87	1979	2	74	23	14	1505
205874	1365496	1.314	4	6.57	66	344	2	<1	0.48	6	17	138	91	2.51	0.05	12	0.62	169	<1	117	415	365	2.50	<5	5	<10	82	1939	<2	71	15	13	784
205875	1365497	0.087	3	8.10	39	400	2	<1	1.82	5	20	173	46	2.93	0.08	19	1.24	478	5	141	492	65	1.89	7	<5	<10	135	2592	<2	81	11	17	252
205876	1365498	0.137	3	7.79	17	439	2	3	1.61	5	26	160	57	3.75	0.15	21	1.49	566	<1	108	563	54	1.53	5	<5	<10	132	3002	<2	98	13	18	93
205877	1365499	1.310	6	9.57	79	479	2	2	0.58	11	20	145	167	3.09	0.21	24	0.78	236	<1	112	439	1042	3.06	20	8	<10	91	2590	<2	90	32	16	2213
205878	1365500	4.799	72	3.79	48	484	<2	<1	1.33	24	16	36	57	3.33	0.17	7	0.94	518	<1	58	577	679	0.70	52	<5	265	251	1958	<2	94	62	14	1971
205879	1365501	0.065	2	6.08	50	451	3	<1	1.32	<4	9	75	25	1.98	0.19	12	1.03	539	2	114	502	74	1.60	<5	<5	<10	116	1425	<2	36	<10	10	157
205880D	1365501	0.073	2	6.08	49	436	2	<1	1.31	<4	9	67	24	1.90	0.18	12	1.01	524	<1	96	493	72	1.62	5	<5	<10	116	1374	2	35	13	10	147
205881	1365502	0.137	4	7.16	47	457	2	<1	0.27	4	7	47	100	1.84	0.20	13	0.54	115	2	84	438	218	1.94	<5	14	<10	88	1608	<2	35	17	8	604
205882	1365503	0.971	5	7.15	87	434	2	<1	0.15	7	7	37	96	2.49	0.19	11	0.46	<100	<1	73	413	208	3.12	6	<5	<10	80	1493	6	32	23	8	1260
205883	1365504	0.201	3	7.68	53	499	2	<1	1.16	<4	7	38	20	1.82	0.22	16	0.96	386	2	72	500	41	1.83	<5	7	<10	115	1801	3	39	11	9	204

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/20/2012
 Date Completed: 08/07/2012
 Job #: 201242758
 Reference: TL12269
 Sample #: 82

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
205884	1365505	0.686	2	6.32	48	420	<2	<1	1.50	4	14	84	36	2.44	0.15	11	1.11	511	<1	93	540	57	1.62	<5	8	<10	137	2132	5	58	14	11	215
205885	1365506	0.138	2	5.26	40	398	2	<1	1.63	<4	13	98	52	2.39	0.10	9	1.00	454	<1	96	518	33	1.69	<5	8	<10	122	2082	4	61	<10	12	70
205886	1365507	0.406	6	6.28	73	484	2	<1	0.58	9	10	48	101	2.46	0.10	11	0.68	193	<1	74	430	312	2.86	<5	14	<10	97	1650	<2	40	30	9	2018
205887	1365508	0.819	4	3.98	44	436	2	<1	0.16	6	7	40	151	2.09	0.12	4	0.49	117	<1	79	408	240	2.12	<5	11	<10	87	1361	<2	32	18	6	851
205888	1365509	0.057	3	5.38	15	492	2	<1	1.16	5	10	32	70	2.39	0.15	12	0.94	402	<1	70	465	238	1.71	6	13	<10	104	1706	4	35	19	7	695
205889	1365510	0.007	3	4.70	15	421	<2	<1	2.37	5	17	54	25	3.45	0.48	9	1.44	677	<1	54	621	9	0.33	6	11	<10	293	2829	5	119	21	17	64
205890	1365511	0.022	2	4.26	10	397	2	<1	1.03	<4	6	32	100	1.33	0.49	10	0.86	327	3	63	466	31	0.80	<5	9	<10	83	1470	<2	34	11	6	69
205891D	1365511	0.020	2	2.34	12	309	2	<1	0.90	<4	6	34	100	1.30	0.12	4	0.77	310	1	68	463	27	0.70	<5	9	<10	71	1193	<2	27	<10	5	74
205892	1365512	0.012	4	7.08	13	517	2	<1	2.58	<4	9	24	15	2.01	0.20	19	1.52	552	<1	49	485	96	1.07	<5	<5	<10	134	1755	10	37	12	8	155
205893	1365513	0.007	2	5.42	10	543	<2	<1	2.09	6	9	26	11	1.93	0.05	15	1.37	489	<1	47	527	38	0.80	7	<5	<10	139	1817	7	38	11	7	1038

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, October 25, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 09/21/2012
 Date Completed: 10/09/2012
 Job #: 201243722
 Reference: TL 12 270
 Sample #: 55

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
273442	1365957	0.030	<1	4.06	38	373	<2	26	1.12	<4	8	24	12	1.42	0.34	3	0.69	338	<1	32	537	15	1.18	<5	13	<10	109	1581	<2	35	<10	6	61
273443	1365958	0.063	1	4.30	34	456	<2	21	0.91	<4	7	18	23	1.41	0.37	3	0.46	294	<1	35	499	39	1.42	<5	18	<10	114	1587	<2	30	<10	5	93
273444	1365959	0.046	1	4.99	36	591	<2	25	1.75	<4	8	21	18	1.52	0.19	6	0.87	445	<1	39	557	22	1.45	<5	18	<10	130	1657	<2	34	<10	5	50
273445	1365960	0.250	<1	0.89	374	>5000	<2	18	0.66	4	6	14	30	2.60	0.07	<1	0.07	<100	<1	16	<100	13	1.04	17	25	<10	97	942	6	15	52	7	15
273446	1365961	0.052	<1	5.27	53	863	<2	20	1.84	<4	7	23	23	1.69	0.29	6	0.88	527	<1	37	509	27	1.72	<5	17	<10	135	1661	2	33	<10	5	66
273447	1365962	0.034	<1	4.49	37	531	<2	18	1.10	<4	7	22	10	1.57	0.33	6	0.74	393	<1	35	396	24	1.79	<5	15	<10	113	1597	<2	32	<10	5	46
273448	1365963	0.108	1	3.96	43	509	<2	26	1.26	4	7	16	46	1.54	0.20	4	0.92	415	<1	35	653	87	1.79	<5	16	<10	111	1544	2	29	<10	5	473
273449	1365964	0.098	1	3.39	33	628	<2	23	0.21	<4	6	13	13	1.26	0.25	2	0.38	204	<1	32	549	83	1.60	7	15	<10	75	1746	<2	30	<10	3	155
273450	1365965	0.024	<1	5.37	32	558	<2	21	1.75	<4	6	20	13	1.23	0.16	4	0.79	462	<1	45	573	25	0.95	<5	23	<10	130	1732	9	31	<10	6	34
273451	1365966	0.012	<1	4.40	31	535	<2	17	1.22	<4	5	18	6	1.25	0.26	4	0.71	376	<1	39	598	19	1.07	<5	21	<10	134	1550	<2	26	<10	5	30
273452D	1365966	0.012	<1	4.08	33	498	<2	14	1.09	<4	4	19	6	1.30	0.26	4	0.73	386	<1	41	615	13	1.08	<5	15	<10	121	1559	<2	26	<10	6	30
273453	1365967	0.020	1	4.99	26	543	<2	16	1.71	<4	5	21	15	1.31	0.40	4	0.57	335	<1	39	662	24	1.12	<5	22	12	139	1522	<2	32	<10	5	34
273454	1365968	0.011	1	5.68	21	515	<2	20	1.71	<4	4	24	18	1.34	0.18	6	0.54	352	<1	49	578	18	1.04	<5	19	<10	155	1569	<2	31	<10	6	30
273455	1365969	0.019	<1	4.12	33	450	<2	18	1.13	<4	4	19	11	1.45	0.24	4	0.57	369	<1	37	492	14	1.22	<5	20	<10	128	1448	<2	27	<10	5	40
273456	1365970	0.006	<1	5.27	18	445	<2	16	2.25	5	15	50	24	3.34	0.38	5	1.29	678	<1	32	608	7	0.49	<5	14	<10	271	2903	<2	115	21	16	50
273457	1365971	0.010	1	4.60	24	583	<2	16	1.06	<4	5	19	11	1.61	0.28	5	0.63	351	<1	34	529	18	1.45	<5	20	<10	172	1567	6	32	<10	6	56
273458	1365972	0.013	<1	5.95	32	483	<2	24	1.70	4	10	56	20	2.45	0.22	15	0.83	679	<1	54	500	13	1.84	<5	22	<10	289	1878	4	46	<10	8	75
273459	1365973	0.032	<1	4.65	47	500	<2	18	1.18	4	19	119	41	3.42	0.17	13	0.90	526	<1	87	494	17	2.50	6	12	<10	271	1996	<2	74	<10	10	68
273460	1365974	0.027	<1	5.87	29	523	<2	26	1.63	4	18	104	39	3.33	0.21	17	1.16	478	<1	84	563	14	2.15	<5	19	<10	299	1959	3	75	<10	11	60
273461	1365975	0.009	<1	5.50	30	428	<2	18	1.25	<4	8	42	17	1.98	0.24	14	0.81	326	<1	52	460	16	1.58	5	16	<10	283	1616	<2	39	<10	6	48

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, October 25, 2012

Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 09/21/2012
 Date Completed: 10/09/2012
 Job #: 201243722
 Reference: TL 12 270
 Sample #: 55

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
273462	1365976	0.011	<1	4.65	30	411	<2	20	0.99	<4	9	41	13	2.03	0.17	13	0.81	321	<1	50	463	16	1.61	6	15	<10	240	1557	<2	37	<10	7	46
273463D	1365976	0.009	<1	4.71	29	393	<2	11	0.99	<4	8	40	13	1.96	0.23	12	0.79	311	<1	52	459	14	1.58	<5	19	<10	240	1508	<2	36	<10	7	46
273464	1365977	0.020	<1	3.93	29	447	<2	21	1.75	4	15	91	35	3.02	0.23	7	1.12	548	<1	75	504	12	1.96	5	18	<10	254	1674	<2	59	<10	10	48
273465	1365978	0.040	2	6.34	30	460	<2	32	1.99	<4	10	29	13	2.30	0.25	13	0.96	722	<1	40	560	28	1.66	<5	19	<10	206	1874	<2	41	<10	7	71
273466	1365979	0.011	1	4.36	14	353	<2	13	1.51	<4	7	21	6	1.81	0.17	11	0.85	510	<1	37	549	6	0.66	<5	14	<10	143	1684	<2	33	<10	6	48
273467	1365980	4.962	65	3.47	52	461	<2	25	1.07	25	13	29	56	2.78	0.10	<1	0.72	468	<1	26	512	549	0.78	54	20	222	201	1809	4	81	61	12	2381
273468	1365981	0.014	2	4.71	18	392	<2	13	1.54	<4	6	19	7	1.68	0.15	11	0.77	511	<1	32	562	17	0.78	<5	16	13	164	1698	<2	33	<10	7	75
273469	1365982	0.014	1	4.52	18	439	<2	12	1.51	<4	6	18	10	1.72	0.20	11	0.91	586	<1	34	548	24	0.85	<5	16	<10	134	1598	<2	34	<10	6	75
273470	1365983	0.042	1	4.72	42	486	<2	13	0.76	<4	8	14	9	1.57	0.25	7	0.48	292	<1	32	562	55	1.42	<5	14	<10	131	1777	<2	34	<10	5	122
273471	1365984	0.030	1	4.31	33	446	<2	20	1.31	<4	7	15	8	1.75	0.38	8	0.79	476	<1	25	534	40	1.25	<5	11	11	124	1618	4	32	<10	5	120
273472	1365985	0.066	2	3.60	16	337	<2	11	1.69	<4	7	15	8	1.61	0.47	2	0.85	468	<1	29	473	19	0.99	<5	17	<10	163	1207	<2	28	<10	5	64
273473	1365986	0.010	1	4.33	22	283	<2	15	2.12	<4	7	19	10	1.78	0.62	4	1.12	412	<1	35	473	18	1.18	<5	15	<10	168	1259	4	29	<10	6	55
273474D	1365986	0.011	1	4.33	19	283	<2	14	2.12	<4	7	18	10	1.78	0.62	4	1.12	408	<1	34	470	14	1.18	<5	14	<10	163	1248	4	29	<10	5	55
273475	1365987	0.017	<1	<0.01	9	<1	<2	12	<0.01	<4	<1	<1	<1	<0.01	<0.01	<1	<0.01	<100	<1	2	<100	<1	<0.01	<5	12	<10	<3	<100	<2	<2	<10	<2	<1
273476	1365988	0.522	2	4.56	37	294	<2	21	1.04	4	19	117	71	3.26	0.20	5	1.03	560	<1	97	525	49	1.75	<5	16	<10	70	2110	<2	66	<10	13	188
273477	1365989	0.096	<1	5.55	29	421	<2	24	1.84	<4	11	52	18	2.06	0.19	6	1.13	686	<1	46	514	33	1.02	<5	17	12	87	1811	<2	41	<10	9	89
273478	1365990	<0.005	<1	4.08	20	381	<2	24	1.95	4	15	47	23	3.13	0.23	3	1.21	629	<1	30	576	2	0.43	5	16	<10	225	2553	2	106	18	15	46
273479	1365991	0.107	1	4.86	22	418	<2	15	1.29	4	9	42	59	2.20	0.16	5	0.84	546	<1	51	466	32	1.40	<5	16	<10	84	1671	<2	41	<10	8	113
273480	1365992	0.078	1	5.57	32	504	<2	19	1.87	4	7	29	55	2.05	0.17	6	1.16	720	<1	50	493	71	1.43	<5	17	10	110	1587	<2	33	<10	7	414
273481	1365993	0.048	<1	5.35	30	495	<2	17	1.87	4	7	27	37	1.87	0.24	6	1.20	540	<1	46	471	26	1.43	<5	19	<10	119	1458	4	30	<10	6	411

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, October 25, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 09/21/2012
 Date Completed: 10/09/2012
 Job #: 201243722
 Reference: TL 12 270
 Sample #: 55

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
273482	1365994	0.012	<1	6.16	24	496	2	7	2.62	<4	6	24	25	1.78	0.23	7	1.51	677	<1	39	487	13	1.10	<5	21	<10	124	1555	<2	32	<10	6	71
273483	1365995	0.114	<1	5.31	30	470	<2	28	1.10	<4	7	31	45	1.73	0.24	10	0.75	339	<1	56	474	15	1.62	<5	19	<10	95	1733	<2	35	14	6	103
273484	1365996	0.094	<1	5.07	35	472	<2	22	0.97	<4	7	36	45	1.63	0.28	10	0.65	294	<1	63	464	16	1.49	<5	18	11	97	1700	<2	34	<10	5	116
273485D	1365996	0.095	1	3.91	26	397	<2	22	0.83	<4	6	31	40	1.47	0.27	5	0.59	265	<1	58	423	10	1.34	<5	20	<10	87	1405	<2	29	<10	5	109
273486	1365997	0.013	<1	4.21	31	429	<2	26	2.06	<4	6	16	8	1.50	0.16	1	1.16	464	<1	33	455	12	0.98	<5	14	14	109	1262	<2	26	<10	5	78
273487	1365998	0.014	<1	4.32	22	434	<2	9	2.14	<4	6	21	9	1.63	0.25	2	1.23	494	<1	40	483	18	0.99	<5	13	<10	118	1275	<2	27	<10	5	64
273488	1365999	0.013	<1	5.62	18	529	<2	28	1.98	<4	6	27	8	1.73	0.17	7	0.91	434	<1	43	502	15	0.85	<5	19	<10	149	1794	6	34	<10	6	47
273489	1366000	2.021	<1	6.16	20	506	<2	15	2.30	4	17	54	34	3.72	0.30	8	1.34	735	<1	35	643	9	0.59	<5	15	<10	277	3131	8	124	25	16	59
273490	1366001	0.038	<1	5.72	21	602	<2	14	1.72	4	8	22	20	1.76	0.19	9	0.80	407	<1	40	499	26	0.95	<5	15	10	123	2022	<2	38	<10	5	209
273491	1366002	0.006	<1	6.20	15	691	3	13	1.94	<4	7	22	12	1.74	0.36	11	0.85	385	<1	40	531	14	0.79	<5	17	<10	132	1989	<2	37	<10	6	65
273492	1366003	0.005	<1	6.71	20	685	2	19	2.67	<4	8	25	9	1.92	0.36	12	1.18	465	<1	45	507	11	0.86	<5	18	<10	144	2109	<2	39	<10	6	86
273493	1366004	0.010	<1	4.95	28	430	<2	<1	2.15	<4	5	19	30	1.66	0.25	6	1.12	429	<1	34	514	20	0.71	<5	24	10	114	1481	<2	28	<10	6	135
273494	1366005	0.047	<1	2.77	27	303	<2	27	1.22	<4	7	20	26	1.60	0.12	<1	0.78	349	<1	42	508	20	1.10	<5	18	<10	89	1204	<2	23	<10	5	183
273495	1366006	0.036	<1	5.09	26	429	<2	25	2.04	4	7	23	28	1.69	0.20	6	1.13	518	<1	41	520	17	0.88	<5	17	<10	119	1553	2	29	<10	6	366
273496D	1366006	0.026	<1	5.73	27	474	<2	29	2.13	4	8	27	26	1.72	0.19	8	1.14	526	<1	47	527	14	0.90	<5	19	10	124	1679	<2	32	<10	6	279
273497	1366007	0.021	<1	5.67	18	442	2	22	1.52	7	8	20	41	1.59	0.17	8	0.86	422	<1	34	530	9	1.07	<5	14	<10	109	1778	<2	33	14	6	948
273498	1366008	0.034	<1	4.74	20	289	4	18	3.32	<4	7	16	19	2.11	0.16	4	1.71	772	<1	27	504	10	0.80	<5	18	<10	121	1590	<2	31	167	6	119
273499	1366009	0.028	<1	3.83	16	337	<2	20	1.86	<4	7	23	32	1.74	0.20	3	1.02	439	<1	41	509	13	0.88	<5	22	<10	97	1360	<2	26	<10	5	117
273500	1366010	<0.005	<1	4.17	15	399	<2	18	2.06	4	15	48	24	3.24	0.26	2	1.26	647	<1	31	608	<1	0.39	5	17	<10	240	2687	<2	110	21	15	56
273501	1366011	0.084	<1	5.30	44	459	<2	14	1.73	<4	7	21	8	1.94	0.23	8	0.93	395	<1	36	496	10	1.69	<5	17	10	83	1786	<2	35	<10	5	43

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, October 9, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 09/21/2012
 Date Completed: 10/09/2012
 Job #: 201243722
 Reference: TL 12 270
 Sample #: 55

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
273442	1365957	30	<0.001	0.030
273443	1365958	63	0.002	0.063
273444	1365959	46	0.001	0.046
273445	1365960	250	0.007	0.250
273446	1365961	52	0.002	0.052
273447	1365962	34	<0.001	0.034
273448	1365963	108	0.003	0.108
273449	1365964	98	0.003	0.098
273450	1365965	24	<0.001	0.024
273451	1365966	12	<0.001	0.012
273452 Dup	1365966	12	<0.001	0.012
273453	1365967	20	<0.001	0.020
273454	1365968	11	<0.001	0.011
273455	1365969	19	<0.001	0.019
273456	1365970	6	<0.001	0.006
273457	1365971	10	<0.001	0.010
273458	1365972	13	<0.001	0.013
273459	1365973	32	<0.001	0.032
273460	1365974	27	<0.001	0.027
273461	1365975	9	<0.001	0.009
273462	1365976	11	<0.001	0.011
273463 Dup	1365976	9	<0.001	0.009
273464	1365977	20	<0.001	0.020
273465	1365978	40	0.001	0.040
273466	1365979	11	<0.001	0.011
273467	1365980	4962	0.145	4.962
273468	1365981	14	<0.001	0.014
273469	1365982	14	<0.001	0.014
273470	1365983	42	0.001	0.042
273471	1365984	30	<0.001	0.030

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, October 9, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 09/21/2012
 Date Completed: 10/09/2012
 Job #: 201243722
 Reference: TL 12 270
 Sample #: 55

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
273472	1365985	66	0.002	0.066
273473	1365986	10	<0.001	0.010
273474 Dup	1365986	11	<0.001	0.011
273475	1365987	17	<0.001	0.017
273476	1365988	522	0.015	0.522
273477	1365989	96	0.003	0.096
273478	1365990	<5	<0.001	<0.005
273479	1365991	107	0.003	0.107
273480	1365992	78	0.002	0.078
273481	1365993	48	0.001	0.048
273482	1365994	12	<0.001	0.012
273483	1365995	114	0.003	0.114
273484	1365996	94	0.003	0.094
273485 Dup	1365996	95	0.003	0.095
273486	1365997	13	<0.001	0.013
273487	1365998	14	<0.001	0.014
273488	1365999	13	<0.001	0.013
273489	1366000	2021	0.059	2.021
273490	1366001	38	0.001	0.038
273491	1366002	6	<0.001	0.006
273492	1366003	5	<0.001	0.005
273493	1366004	10	<0.001	0.010
273494	1366005	47	0.001	0.047
273495	1366006	36	0.001	0.036
273496 Dup	1366006	26	<0.001	0.026
273497	1366007	21	<0.001	0.021
273498	1366008	34	<0.001	0.034
273499	1366009	28	<0.001	0.028
273500	1366010	<5	<0.001	<0.005
273501	1366011	84	0.002	0.084

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012

Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/25/2012
 Date Completed: 08/14/2012
 Job #: 201242815
 Reference: TL 12 271
 Sample #: 289

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
212787	1369409	<0.005	<1	3.98	15	44	<2	7	5.76	6	42	200	98	8.00	<0.01	9	3.32	1850	<1	110	297	13	0.51	6	19	14	136	3953	<2	227	<10	17	62
212788	1369410	<0.005	<1	2.98	14	67	<2	12	5.80	6	43	78	129	8.89	0.03	8	3.73	1852	<1	102	797	9	0.57	<5	10	15	81	4610	<2	264	13	21	83
212789	1369411	<0.005	<1	3.24	11	84	<2	7	5.15	5	40	81	178	7.45	0.03	<1	3.04	1600	<1	95	383	12	0.54	6	12	15	107	4085	<2	229	<10	17	65
212790	1369412	0.006	<1	3.98	12	22	<2	5	4.76	5	38	97	115	7.50	<0.01	4	3.15	1546	<1	90	369	11	0.42	5	10	15	112	4283	<2	242	<10	17	73
212791	1369413	<0.005	<1	3.56	12	53	<2	8	4.91	4	37	237	91	6.08	<0.01	2	3.23	1220	<1	108	258	11	0.37	<5	12	14	119	3551	<2	198	<10	14	57
212792	1369414	0.009	<1	3.91	13	177	<2	8	5.24	5	40	210	87	7.02	<0.01	11	3.86	1425	<1	113	285	15	0.47	7	14	16	129	3867	<2	223	<10	15	67
212793	1369415	<0.005	<1	1.66	13	9	<2	8	6.05	4	55	611	101	6.08	0.03	7	8.84	1057	<1	482	301	12	0.63	5	17	19	69	2598	<2	89	<10	9	54
212794	1369416	0.007	<1	3.52	13	84	2	7	5.60	5	40	286	47	6.98	0.01	14	5.67	1742	<1	216	388	15	0.45	<5	16	17	158	3025	6	177	<10	13	69
212795	1369417	0.026	<1	2.27	11	29	<2	3	4.78	4	33	138	51	5.91	0.13	2	3.10	1728	<1	101	306	16	0.34	8	17	13	121	3062	<2	181	<10	13	66
212796	1369418	0.023	<1	4.43	12	22	<2	10	5.77	5	37	147	100	7.58	0.19	8	3.35	2055	<1	107	259	13	0.52	8	14	15	123	3314	<2	202	<10	14	61
212797D	1369418	0.017	<1	3.31	11	12	<2	9	5.62	5	37	146	104	7.54	0.16	6	3.27	2032	<1	106	263	13	0.46	6	16	16	111	3180	<2	198	<10	14	62
212798	1369419	0.009	<1	4.19	15	9	<2	6	5.25	5	40	135	89	6.79	0.22	13	3.25	1622	<1	103	254	12	0.51	<5	15	13	128	3471	<2	209	<10	14	44
212799	1369420	1.862	<1	<0.01	8	<1	<2	8	<0.01	<4	<1	<1	4	0.07	<0.01	<1	0.16	<100	<1	38	<100	11	0.36	<5	16	12	26	133	3	2	<10	2	<1
212800	1369421	0.014	<1	2.23	14	6	<2	2	4.39	5	37	108	57	6.76	<0.01	8	3.65	1177	<1	98	257	16	0.31	5	12	15	81	3072	<2	202	<10	13	44
212801	1369422	0.011	<1	3.54	8	17	<2	<1	4.77	5	39	58	57	7.57	<0.01	8	3.42	1205	<1	103	323	9	0.42	5	13	17	110	3769	<2	227	<10	17	48
212802	1369423	0.011	<1	4.50	11	13	<2	18	5.17	6	44	72	128	8.97	<0.01	8	3.19	1551	<1	116	363	10	0.43	5	16	18	121	4430	<2	263	<10	20	103
212803	1369424	0.013	<1	3.57	12	9	<2	9	4.59	5	43	18	52	8.55	<0.01	8	2.77	1539	<1	80	380	10	0.47	9	15	13	114	4782	<2	280	10	20	46
212804	1369425	0.007	<1	4.48	12	5	2	13	5.45	6	53	20	101	9.45	0.08	21	3.33	1610	<1	109	380	12	0.58	7	13	16	122	4738	<2	286	<10	19	46
212805	1369426	0.012	<1	4.07	13	<1	<2	7	5.44	6	48	10	86	8.45	0.02	19	3.06	1430	<1	85	333	16	0.55	9	11	18	98	4201	<2	263	<10	17	46
212806	1369427	0.018	<1	3.20	12	19	<2	9	5.06	5	41	30	110	7.68	0.09	5	3.18	1367	<1	107	278	8	0.36	5	10	14	133	3571	<2	226	<10	15	70

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012

Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/25/2012
 Date Completed: 08/14/2012
 Job #: 201242815
 Reference: TL 12 271
 Sample #: 289

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
212807	1369428	0.027	7	3.99	15	11	<2	6	5.78	5	40	28	74	7.16	0.09	11	3.40	1318	<1	102	240	12	0.36	5	10	14	187	3448	<2	220	<10	14	48
212808D	1369428	0.014	<1	3.99	12	11	<2	14	5.68	5	39	30	80	7.06	0.08	11	3.34	1302	<1	105	243	11	0.35	7	15	11	185	3387	<2	216	<10	14	41
212809	1369429	0.023	<1	3.50	11	21	<2	2	5.08	4	33	211	92	5.74	0.18	4	3.34	1125	<1	103	211	11	0.33	8	17	14	146	2824	3	174	<10	12	49
212810	1369430	0.017	<1	2.91	14	5	2	14	6.09	4	38	566	36	5.65	0.15	14	5.21	1169	<1	182	504	9	0.35	6	12	14	117	2691	<2	150	<10	12	43
212811	1369431	0.018	<1	3.97	22	41	<2	6	6.66	4	39	584	63	6.14	0.02	12	4.61	1225	<1	166	427	15	0.40	5	20	16	128	2571	<2	160	<10	13	38
212812	1369432	0.024	<1	3.96	16	10	<2	10	5.65	5	40	260	81	7.14	<0.01	10	3.76	1258	<1	128	331	12	0.39	8	13	15	157	3302	<2	200	<10	15	56
212813	1369433	0.036	<1	3.65	10	11	<2	8	6.04	4	36	230	106	6.45	<0.01	4	3.51	1083	<1	125	296	8	0.39	5	11	15	119	3001	<2	188	<10	13	53
212814	1369434	0.007	<1	2.66	10	7	<2	13	4.62	5	55	772	88	7.72	<0.01	15	6.27	1377	<1	262	203	15	0.37	8	16	18	62	2531	<2	168	<10	11	68
212815	1369435	0.009	<1	3.20	12	45	<2	10	5.17	4	38	315	100	6.49	<0.01	7	4.03	1100	<1	131	333	8	0.42	6	15	16	115	3079	3	189	<10	14	55
212816	1369436	0.020	<1	3.17	14	13	<2	4	5.00	5	38	233	89	7.24	<0.01	5	3.46	1101	<1	101	242	11	0.31	8	14	13	128	2905	<2	194	<10	14	62
212817	1369437	0.021	<1	3.80	11	18	<2	8	4.79	5	49	427	167	7.71	0.01	16	4.97	1315	<1	168	259	11	0.39	7	12	14	93	3048	<2	195	<10	14	85
212818	1369438	<0.005	<1	3.46	10	13	<2	10	4.78	5	38	246	62	7.04	0.03	7	3.67	1261	<1	108	249	16	0.32	<5	12	12	102	3017	<2	196	<10	13	61
212819D	1369438	<0.005	<1	3.32	11	11	<2	8	4.84	5	39	251	64	7.15	0.03	7	3.72	1288	<1	116	238	12	0.32	9	9	16	101	3010	<2	198	<10	14	57
212820	1369439	<0.005	<1	2.91	14	7	<2	9	4.12	6	52	557	34	7.81	0.02	21	5.65	1390	<1	222	237	15	0.36	10	9	15	58	2723	5	179	<10	12	86
212821	1369440	0.016	<1	<0.01	12	<1	<2	<1	<0.01	<4	<1	<1	<1	0.08	<0.01	<1	0.09	<100	<1	9	<100	12	0.08	<5	17	12	6	<100	<2	2	<10	<2	<1
212822	1369441	<0.005	<1	2.92	16	37	<2	10	3.91	5	42	266	108	7.74	<0.01	21	4.20	1608	<1	114	233	10	0.31	6	10	10	68	3114	<2	218	<10	14	89
212823	1369442	<0.005	<1	2.71	18	<1	<2	16	4.65	6	62	967	14	8.38	<0.01	29	7.54	1713	<1	348	174	15	0.31	9	13	17	37	2246	2	163	<10	11	68
212824	1369443	<0.005	<1	2.89	15	<1	<2	15	4.67	5	62	1411	40	7.70	<0.01	57	9.40	2275	<1	413	118	13	0.35	6	20	15	29	1502	4	119	<10	8	57
212825	1369444	<0.005	<1	<0.01	16	<1	<2	8	1.48	6	92	3166	9	8.84	<0.01	1	>10.00	1339	<1	976	<100	11	0.35	10	17	15	31	944	4	78	<10	5	51
212826	1369445	<0.005	<1	<0.01	17	<1	<2	16	1.07	5	106	2873	12	8.67	<0.01	<1	>10.00	1219	<1	1034	<100	11	0.27	11	12	15	28	878	<2	69	<10	4	50

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012

Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/25/2012
 Date Completed: 08/14/2012
 Job #: 201242815
 Reference: TL 12 271
 Sample #: 289

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
212827	1369446	<0.005	<1	0.08	16	<1	<2	18	1.27	4	110	3007	13	8.94	<0.01	<1	>10.00	1284	<1	1100	<100	14	0.34	13	16	16	33	966	<2	73	<10	5	55
212828	1369447	<0.005	<1	<0.01	16	<1	<2	10	1.60	5	109	3219	32	8.28	0.05	<1	>10.00	1228	<1	1034	<100	19	0.28	10	17	15	33	878	6	76	<10	4	59
212829	1369448	<0.005	<1	<0.01	15	<1	<2	4	1.19	5	103	3256	13	8.29	0.04	<1	>10.00	1254	<1	1000	<100	12	0.32	10	15	17	32	900	<2	74	<10	4	63
212830D	1369448	<0.005	<1	<0.01	11	<1	<2	17	1.24	6	109	3453	17	8.80	0.05	<1	>10.00	1329	<1	1068	<100	18	0.27	12	13	17	28	940	5	76	<10	4	92
212831	1369449	<0.005	<1	<0.01	13	<1	2	16	1.05	5	110	3584	13	8.61	0.04	<1	>10.00	1310	<1	1083	<100	18	0.32	12	12	15	30	973	<2	78	<10	4	65
212832	1369450	<0.005	<1	<0.01	16	<1	<2	16	1.37	5	105	3506	9	8.51	0.11	<1	>10.00	1305	<1	1031	<100	15	0.31	9	9	14	31	932	<2	78	<10	5	63
212833	1369451	<0.005	<1	<0.01	15	<1	<2	3	1.32	5	102	3182	11	8.01	0.16	<1	>10.00	1364	<1	941	<100	15	0.29	10	17	15	31	822	<2	67	<10	4	62
212834	1369452	<0.005	<1	0.35	16	<1	<2	12	1.95	5	104	3462	7	7.70	0.15	<1	>10.00	1558	<1	929	<100	14	0.32	9	14	15	43	976	<2	72	<10	4	57
212835	1369453	<0.005	<1	0.80	14	<1	<2	13	2.22	4	136	3833	44	7.68	<0.01	<1	>10.00	1590	<1	981	<100	17	0.36	9	11	18	40	1034	2	75	<10	5	67
212836	1369454	<0.005	<1	1.01	15	<1	<2	6	1.51	6	87	4237	5	8.71	<0.01	<1	>10.00	1681	<1	1007	<100	11	0.38	9	10	15	34	1183	3	79	<10	4	69
212837	1369455	<0.005	<1	0.96	16	<1	<2	9	1.85	5	94	3724	7	7.96	<0.01	<1	>10.00	1537	<1	998	<100	13	0.40	9	12	17	38	1208	4	77	<10	6	59
212838	1369456	<0.005	<1	0.16	19	<1	<2	5	1.78	5	107	3756	20	8.80	<0.01	<1	>10.00	1438	<1	1066	<100	19	0.36	11	6	14	36	987	2	86	<10	6	65
212839	1369457	<0.005	<1	0.03	13	<1	<2	14	1.61	5	106	3437	18	8.68	<0.01	<1	>10.00	1420	<1	1019	<100	10	0.34	14	10	17	33	1016	<2	79	<10	5	65
212840	1369458	<0.005	<1	0.21	13	<1	<2	7	1.53	5	112	3609	30	8.90	<0.01	<1	>10.00	1383	<1	1060	<100	12	0.35	11	20	22	33	1034	<2	82	<10	5	80
212841D	1369458	0.006	<1	0.50	14	<1	<2	8	1.52	6	109	3522	30	8.69	<0.01	<1	>10.00	1355	<1	1046	<100	12	0.39	12	21	15	36	1047	3	83	<10	5	86
212842	1369459	<0.005	<1	0.74	18	<1	<2	8	1.58	5	107	3504	16	8.60	0.11	<1	>10.00	1361	<1	1021	<100	20	0.41	11	16	10	36	1041	7	82	<10	5	113
212843	1369460	5.115	<1	<0.01	11	<1	<2	20	<0.01	<4	1	20	3	0.09	0.05	<1	0.30	<100	<1	48	<100	13	0.43	6	23	12	31	145	5	2	<10	3	<1
212844	1369461	<0.005	<1	0.83	13	<1	<2	3	1.61	5	97	3163	18	7.96	<0.01	<1	>10.00	1210	<1	904	<100	13	0.42	9	14	16	38	1005	5	76	<10	5	59
212845	1369462	0.012	<1	0.65	15	<1	<2	12	1.47	6	98	3103	20	7.98	<0.01	<1	>10.00	1165	<1	902	<100	13	0.40	10	14	14	36	971	3	77	<10	5	58
212846	1369463	0.018	<1	1.41	13	<1	<2	11	1.65	5	101	3080	14	8.12	<0.01	<1	>10.00	1168	<1	934	<100	12	0.46	12	11	17	42	1082	<2	82	<10	6	60

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012

Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/25/2012
 Date Completed: 08/14/2012
 Job #: 201242815
 Reference: TL 12 271
 Sample #: 289

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
212847	1369464	0.021	<1	2.26	16	<1	<2	14	1.82	5	93	2804	27	7.93	<0.01	<1	>10.00	1311	<1	844	141	13	0.58	9	18	14	48	1082	4	80	<10	7	71
212848	1369465	0.014	<1	0.43	15	<1	<2	13	1.52	5	93	2990	12	7.84	<0.01	<1	>10.00	1401	<1	881	<100	15	0.36	12	12	15	31	1045	4	81	<10	5	72
212849	1369466	0.009	<1	2.03	14	<1	<2	13	1.69	5	96	3005	15	7.94	<0.01	<1	>10.00	1422	<1	895	<100	16	0.54	11	17	19	43	1153	<2	87	<10	7	83
212850	1369467	0.007	<1	2.48	17	<1	<2	4	2.08	5	90	2897	20	7.91	<0.01	<1	>10.00	1367	<1	852	<100	13	0.56	8	13	12	48	1264	<2	93	<10	7	70
212851	1369468	0.019	<1	2.71	13	<1	<2	12	2.55	5	80	2636	33	7.83	0.08	<1	>10.00	1388	<1	742	<100	7	0.58	6	10	18	56	1370	3	101	<10	8	74
212852R	1369468	0.013	<1	<0.01	12	<1	<2	9	1.34	4	53	1611	23	5.11	<0.01	<1	6.90	859	<1	493	<100	11	0.31	<5	9	14	36	902	<2	66	<10	5	42
212853	1369469	0.016	<1	4.48	15	6	2	11	2.96	6	84	2596	20	8.40	<0.01	7	>10.00	1535	<1	746	144	12	0.74	9	15	16	71	1532	4	110	<10	9	107
212854	1369470	0.029	<1	5.24	17	9	<2	19	3.29	6	84	2567	61	8.59	<0.01	8	>10.00	1611	<1	731	174	18	0.76	10	18	16	77	1608	4	118	<10	9	92
212855	1369471	0.015	<1	5.68	12	11	<2	16	3.61	6	76	2300	59	8.52	0.07	9	>10.00	1708	<1	665	198	16	0.76	13	18	16	84	1696	<2	126	<10	10	89
212856	1369472	0.013	<1	5.62	14	412	<2	9	3.94	6	69	1878	9	8.24	0.10	53	9.32	1547	<1	554	172	16	0.68	9	17	15	82	2417	3	165	<10	13	91
212857	1369473	0.023	2	6.25	13	327	<2	17	4.29	6	76	2006	90	8.29	0.04	63	9.51	1570	<1	600	182	16	0.80	8	16	15	93	2172	<2	151	<10	11	104
212858	1369474	0.015	<1	5.52	12	641	<2	8	3.82	6	65	1836	30	7.72	<0.01	79	8.76	1394	<1	528	160	16	0.77	12	12	12	85	2302	3	155	<10	12	87
212859	1369475	0.017	<1	6.39	19	319	2	17	3.83	5	57	1583	67	6.76	0.03	26	8.06	1306	<1	500	740	21	0.80	7	23	14	378	2654	<2	115	<10	15	78
212860	1369476	0.013	<1	5.54	17	16	<2	16	5.07	6	77	2329	125	8.53	0.10	35	>10.00	1665	<1	666	146	17	0.79	10	8	18	71	1870	2	149	<10	10	62
212861	1369477	0.023	<1	4.91	12	111	<2	22	4.28	5	62	1784	118	8.12	0.11	45	9.13	1512	<1	513	112	19	0.71	5	17	14	88	1966	<2	146	<10	11	64
212862	1369478	0.043	<1	6.43	14	217	<2	20	3.57	5	67	1834	35	8.35	0.18	60	9.07	1383	<1	558	175	18	0.69	9	16	16	121	2365	3	165	<10	12	74
212863D	1369478	0.013	<1	5.65	17	207	<2	9	3.39	5	67	1790	33	8.11	0.20	56	8.83	1340	<1	532	164	16	0.62	10	16	16	114	2276	<2	160	<10	11	73
212864	1369479	<0.005	<1	5.41	12	212	<2	8	3.61	5	64	1519	7	8.01	0.23	56	8.52	1331	<1	494	203	12	0.61	6	22	13	124	2372	4	158	<10	12	82
212865	1369480	0.005	<1	2.54	6	13	2	6	0.10	<4	<1	7	4	0.11	<0.01	8	0.39	<100	<1	44	<100	16	0.82	<5	15	14	57	284	<2	4	<10	5	<1
212866	1369481	0.015	<1	4.87	14	190	<2	10	3.35	6	62	1634	4	8.01	<0.01	52	8.25	1293	<1	484	169	17	0.52	7	11	16	116	2249	3	162	<10	12	72

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/25/2012
 Date Completed: 08/14/2012
 Job #: 201242815
 Reference: TL 12 271
 Sample #: 289

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
212867	1369482	0.016	<1	4.95	14	141	<2	4	3.29	5	59	1402	12	7.49	<0.01	43	7.68	1237	<1	443	283	18	0.62	8	12	18	120	2245	<2	158	<10	12	68
212868	1369483	0.014	<1	3.56	19	147	<2	6	3.83	5	61	1419	6	7.63	<0.01	41	7.84	1287	<1	452	449	11	0.48	7	14	14	86	2122	5	141	<10	12	95
212869	1369484	0.023	<1	3.35	15	67	<2	17	4.09	5	57	1742	6	7.36	<0.01	32	7.64	1260	<1	485	188	9	0.47	5	25	15	112	2052	2	140	<10	11	100
212870	1369485	0.007	<1	4.81	18	423	<2	5	4.26	4	46	650	93	6.03	0.07	28	5.38	941	<1	274	833	20	0.82	<5	9	16	393	2751	2	135	<10	13	87
212871	1369486	0.010	<1	7.00	19	329	<2	8	4.63	4	49	653	91	6.35	<0.01	35	5.64	1009	<1	315	961	11	1.07	6	17	15	412	3066	<2	141	<10	15	78
212872	1369487	<0.005	<1	6.45	17	58	2	1	1.40	<4	100	46	401	4.64	0.07	7	1.16	335	<1	125	781	12	2.02	7	21	12	201	3449	<2	78	<10	21	120
212873	1369488	0.006	<1	6.95	15	111	<2	<1	1.95	4	86	369	546	5.96	0.05	16	1.78	402	2	212	554	13	2.63	<5	13	15	256	3135	<2	83	<10	16	91
212874D	1369488	0.009	<1	7.48	13	116	2	<1	2.03	4	89	378	559	6.08	0.03	18	1.83	410	2	206	570	14	2.73	6	11	14	265	3203	<2	85	<10	16	91
212875	1369489	0.010	<1	7.70	19	235	2	17	5.37	12	42	463	71	8.54	0.14	57	3.98	874	<1	172	422	19	0.92	<5	20	16	378	7313	3	265	17	17	1570
212876	1369490	<0.005	<1	6.29	11	184	<2	9	5.78	5	48	838	25	7.35	0.09	47	4.74	866	<1	247	333	15	0.63	5	16	12	380	5854	<2	221	49	13	69
212877	1369491	0.007	<1	2.23	14	313	<2	5	4.01	5	66	1879	14	7.73	<0.01	71	7.57	973	<1	601	269	8	0.40	<5	8	16	80	3632	<2	164	<10	9	66
212878	1369492	<0.005	2	2.01	12	336	2	4	3.17	<4	33	663	38	4.38	<0.01	26	4.06	607	<1	326	863	21	0.45	10	11	16	416	2736	<2	94	18	10	87
212879	1369493	0.008	<1	9.68	18	414	2	8	2.40	<4	22	222	50	3.42	<0.01	43	1.87	450	<1	183	560	16	1.03	<5	18	15	345	2993	<2	56	<10	14	72
212880	1369494	0.014	<1	2.21	13	236	2	<1	2.47	6	31	18	159	9.77	<0.01	20	1.40	979	<1	67	2615	24	0.70	7	10	13	168	3543	<2	24	<10	54	160
212881	1369495	0.019	<1	0.47	13	153	2	11	1.80	7	25	6	27	10.77	<0.01	23	1.32	1259	<1	53	2972	17	0.28	6	9	18	60	2697	<2	6	<10	57	232
212882	1369496	<0.005	<1	4.29	16	37	<2	5	2.44	6	22	28	29	9.07	<0.01	16	1.03	2272	<1	62	2429	18	0.71	7	14	14	101	4838	<2	8	22	50	227
212883	1369497	<0.005	<1	2.34	11	200	<2	10	2.76	6	19	19	13	9.69	0.01	22	1.25	2182	<1	68	2221	15	0.39	6	12	15	92	3241	<2	8	<10	67	278
212884	1369498	0.007	<1	0.11	12	79	<2	7	3.27	6	35	24	49	9.33	<0.01	9	2.06	1217	<1	79	1482	12	0.28	5	19	13	71	2848	<2	205	<10	35	113
212885D	1369498	<0.005	<1	2.01	16	121	<2	12	3.63	6	36	25	50	9.81	0.06	14	2.18	1290	<1	74	1561	14	0.39	7	9	13	140	3903	<2	220	<10	37	118
212886	1369499	0.007	<1	2.88	13	92	<2	13	4.62	6	47	51	80	9.46	0.06	11	2.38	1367	<1	92	1039	10	0.47	11	8	14	168	6292	<2	281	<10	28	104

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012


Final Certificate

Treasury Metals Inc
Exchange Tower 130 King St Suite 3680
Toronto, On, CAN
M5X 1B1
Ph#: (416) 599-4133
Fax#: (416) 599-4959
Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/25/2012
Date Completed: 08/14/2012
Job #: 201242815
Reference: TL 12 271
Sample #: 289

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
212887	1369500	0.269	<1	<0.01	10	<1	<2	11	<0.01	<4	<1	<1	4	0.16	0.03	<1	0.19	<100	<1	40	<100	8	0.43	<5	19	13	31	231	4	5	<10	3	<1
212888	1369501	0.008	<1	4.51	9	354	<2	19	4.03	6	41	47	78	8.57	0.12	32	1.83	1342	<1	79	991	17	0.60	<5	13	22	227	7028	<2	241	<10	26	108
212889	1369502	<0.005	<1	2.77	13	247	2	<1	1.67	<4	14	24	23	3.39	<0.01	15	0.96	469	<1	61	565	18	0.40	<5	10	13	261	2991	<2	82	<10	11	64
212890	1369503	<0.005	<1	2.88	12	21	<2	10	3.81	6	50	36	106	10.51	<0.01	11	2.61	1391	<1	76	1221	12	0.54	<5	11	15	116	5585	<2	322	<10	29	108
212891	1369504	<0.005	<1	1.85	12	71	3	16	4.22	7	52	34	100	10.62	<0.01	19	2.55	1421	<1	85	995	18	0.71	9	11	16	106	5248	<2	294	<10	31	124
212892	1369505	<0.005	<1	3.10	10	36	2	6	4.10	6	47	27	89	10.68	<0.01	16	2.68	1388	<1	77	872	15	0.72	10	16	14	151	5811	<2	312	<10	34	120
212893	1369506	<0.005	<1	2.75	11	31	2	6	4.11	6	49	24	81	10.52	<0.01	13	2.64	1370	<1	76	849	20	0.66	9	13	12	158	5510	<2	313	<10	34	107
212894	1369507	<0.005	<1	2.32	12	301	2	16	3.61	6	43	22	85	8.90	<0.01	15	2.13	1147	<1	72	822	14	0.98	6	14	13	254	5525	<2	256	14	33	99
212895	1369508	<0.005	<1	2.34	14	101	<2	9	4.18	6	50	40	111	10.26	<0.01	14	2.32	1373	<1	87	898	14	0.84	8	9	17	123	5437	<2	289	<10	31	115
212896D	1369508	0.015	<1	2.32	10	100	<2	5	4.21	6	50	38	113	10.34	<0.01	14	2.32	1377	<1	91	901	11	0.82	7	6	13	125	5331	<2	294	<10	31	115
212897	1369509	0.017	<1	1.65	10	47	<2	8	4.12	7	46	33	128	11.13	0.04	13	2.32	1454	<1	81	858	13	0.76	6	11	16	107	4301	<2	322	<10	34	130
212898	1369510	0.024	<1	1.51	15	50	2	9	4.51	6	43	7	87	10.26	0.09	9	2.19	1556	<1	67	964	19	0.62	6	15	17	108	5951	3	283	<10	36	131
212899	1369511	0.055	<1	0.59	12	45	<2	11	4.00	7	44	18	81	10.32	<0.01	8	2.23	1470	<1	66	843	17	1.10	7	13	19	59	4768	<2	286	<10	33	131
212900	1369512	0.027	<1	4.74	16	84	<2	11	3.88	6	49	24	85	10.34	0.14	23	2.41	1449	<1	60	837	11	0.98	<5	10	14	119	7391	<2	306	<10	34	119
212901	1369513	0.012	<1	3.40	17	21	<2	11	3.92	7	52	26	103	10.58	<0.01	15	2.50	1388	<1	71	897	19	0.64	7	18	12	110	5842	<2	304	<10	33	115
212902	1369514	0.021	1	3.41	10	11	<2	7	4.39	7	49	27	106	10.81	<0.01	15	2.53	1451	<1	80	931	14	0.56	7	9	17	125	6524	4	310	<10	35	110
212903	1369515	0.025	<1	2.94	12	47	2	12	4.50	6	49	28	95	10.27	<0.01	16	2.39	1481	<1	80	956	14	0.67	7	13	13	113	6782	<2	308	<10	34	110
212904	1369516	0.010	<1	4.16	13	155	5	14	5.41	7	58	36	106	11.69	<0.01	27	2.52	1779	<1	89	930	17	1.05	7	14	19	147	7271	2	309	<10	36	139
212905	1369517	0.028	<1	5.36	19	454	3	6	1.01	<4	25	155	41	4.60	<0.01	64	1.71	634	<1	128	542	24	0.56	<5	17	16	223	3177	<2	111	<10	15	74
212906	1369518	0.022	<1	4.10	12	473	2	<1	1.30	<4	24	158	47	4.09	<0.01	53	1.74	544	<1	126	680	28	0.51	6	17	19	251	2831	<2	94	<10	15	64

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
Jason Moore, General Manager

The results included on this report relate only to the items tested.
The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/25/2012
 Date Completed: 08/14/2012
 Job #: 201242815
 Reference: TL 12 271
 Sample #: 289

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
212907D	1369518	0.012	<1	4.96	13	480	2	11	1.42	<4	23	164	48	4.13	0.01	55	1.75	547	<1	136	687	26	0.60	7	17	14	264	2901	<2	96	<10	15	63
212908	1369519	0.022	<1	3.89	13	529	2	7	0.80	<4	19	148	43	3.41	0.07	36	1.31	474	<1	122	515	30	0.54	<5	20	17	254	2432	4	72	<10	12	51
212909	1369520	0.016	<1	<0.01	10	<1	<2	11	<0.01	<4	<1	<1	3	0.07	0.10	<1	0.17	<100	<1	30	<100	12	0.40	<5	20	11	29	151	2	3	<10	2	<1
212910	1369521	0.027	<1	4.79	14	551	2	14	1.07	<4	21	172	51	3.73	0.14	34	1.49	532	<1	133	569	32	0.64	7	24	14	300	2694	<2	78	<10	13	75
212911	1369522	0.025	<1	5.16	18	511	2	3	0.82	<4	22	161	47	4.13	<0.01	35	1.62	517	<1	133	567	26	0.58	6	20	13	246	2790	<2	92	<10	15	62
212912	1369523	0.016	<1	5.24	15	501	2	2	1.02	<4	21	170	45	3.81	<0.01	28	1.51	504	<1	149	552	34	0.57	5	15	15	299	2640	3	81	<10	13	59
212913	1369524	0.015	<1	7.84	18	451	2	15	1.11	<4	22	151	45	3.85	<0.01	37	1.63	537	<1	126	539	29	0.86	6	13	19	247	2942	2	95	<10	16	59
212914	1369525	0.011	<1	5.35	13	454	2	10	0.93	<4	19	145	42	3.49	<0.01	29	1.43	497	<1	115	512	30	0.69	7	14	15	259	2556	2	77	<10	12	57
212915	1369526	0.007	<1	5.64	16	451	2	2	1.00	<4	20	149	41	3.57	<0.01	30	1.46	512	<1	119	528	29	0.75	7	14	13	256	2587	<2	78	<10	13	58
212916	1369527	0.009	<1	4.99	18	557	2	12	0.82	<4	18	157	41	3.48	<0.01	28	1.39	475	<1	149	524	26	0.60	<5	18	16	270	2582	2	76	<10	13	53
212917	1369528	0.017	<1	2.65	7	261	<2	3	0.44	<4	10	79	22	1.84	<0.01	15	0.73	249	<1	65	264	16	0.34	<5	7	<10	137	1371	<2	39	<10	7	29
212918R	1369528	0.008	<1	2.58	9	333	<2	6	0.44	<4	13	102	27	2.33	<0.01	14	0.94	317	<1	88	349	20	0.56	<5	16	13	181	1728	<2	51	<10	9	32
212919	1369529	0.013	<1	4.95	12	660	2	22	0.94	<4	22	164	51	3.74	<0.01	28	1.47	518	<1	139	568	29	0.63	7	16	19	298	2859	<2	79	<10	13	59
212920	1369530	0.010	<1	4.10	13	536	2	7	0.64	<4	23	174	47	4.10	0.10	25	1.54	529	<1	152	570	30	0.51	<5	16	18	210	2756	<2	94	<10	14	63
212921	1369531	<0.005	<1	4.75	16	602	2	11	0.82	<4	23	168	47	4.14	0.01	27	1.66	520	<1	140	596	29	0.54	7	10	17	268	2776	<2	94	<10	14	63
212922	1369532	<0.005	<1	5.93	16	544	<2	6	0.81	<4	24	175	47	4.35	0.06	29	1.74	543	<1	142	572	27	0.62	5	19	14	234	2979	5	100	<10	15	70
212923	1369533	<0.005	<1	5.94	14	496	2	11	0.79	<4	25	178	51	4.66	<0.01	28	1.84	594	<1	137	616	31	0.58	7	14	14	228	3061	<2	113	<10	16	72
212924	1369534	<0.005	<1	5.37	13	506	2	<1	0.86	<4	23	161	44	4.27	<0.01	25	1.66	551	<1	142	600	28	0.57	6	11	17	234	2770	2	98	<10	14	74
212925	1369535	0.008	<1	4.77	17	546	2	<1	0.94	<4	23	169	51	4.14	<0.01	28	1.60	548	<1	136	578	30	0.62	7	20	17	261	2870	<2	92	<10	15	67
212926	1369536	<0.005	<1	5.55	17	491	2	3	0.98	<4	24	169	50	4.23	<0.01	28	1.68	532	<1	153	581	31	0.63	7	16	15	257	2804	4	94	<10	15	67

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012

Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/25/2012
 Date Completed: 08/14/2012
 Job #: 201242815
 Reference: TL 12 271
 Sample #: 289

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
212927	1369537	0.007	<1	4.27	15	498	2	10	1.01	<4	20	181	36	3.56	<0.01	20	1.72	495	<1	134	584	26	0.44	6	16	14	268	2462	<2	73	<10	12	56
212928	1369538	<0.005	<1	5.18	13	508	2	7	1.43	<4	12	57	20	2.61	<0.01	15	1.09	411	<1	104	668	24	0.45	6	23	15	325	2255	<2	49	<10	12	53
212929D	1369538	<0.005	<1	5.05	13	502	2	10	1.43	<4	11	63	20	2.59	0.07	15	1.07	406	<1	113	675	27	0.41	6	25	16	328	2209	<2	47	<10	11	52
212930	1369539	<0.005	<1	3.52	12	495	2	1	0.81	<4	20	152	42	3.56	<0.01	20	1.36	487	<1	139	523	27	0.44	6	16	14	285	2454	2	71	<10	12	55
212931	1369540	2.029	<1	<0.01	10	<1	2	15	<0.01	<4	<1	1	4	0.06	<0.01	<1	0.16	<100	<1	40	<100	15	0.40	6	22	15	29	139	<2	2	<10	2	<1
212932	1369541	0.018	<1	3.13	11	554	2	5	0.69	<4	18	110	34	3.29	<0.01	20	1.29	457	<1	95	617	24	0.45	6	23	14	223	2442	6	66	<10	12	59
212933	1369542	0.005	1	5.24	16	565	2	5	1.02	<4	22	171	47	3.98	0.38	26	1.50	549	<1	120	585	34	0.63	7	19	13	290	2986	<2	86	<10	14	61
212934	1369543	<0.005	<1	4.04	15	545	2	8	0.96	<4	23	167	47	3.86	0.42	23	1.62	535	<1	133	627	32	0.51	5	16	15	269	2875	<2	84	10	14	63
212935	1369544	0.011	<1	4.99	15	526	2	<1	0.67	<4	24	199	45	4.42	<0.01	29	1.65	551	3	184	545	29	0.55	6	16	16	216	2801	<2	98	<10	14	77
212936	1369545	<0.005	<1	3.64	16	428	2	5	0.71	<4	21	159	43	3.74	<0.01	21	1.39	513	<1	129	519	29	0.50	<5	16	17	216	2600	3	83	<10	13	60
212937	1369546	0.008	<1	6.18	11	491	2	<1	1.07	<4	23	173	49	4.08	<0.01	30	1.57	571	<1	145	584	28	0.70	7	13	12	269	3065	2	93	<10	15	65
212938	1369547	0.011	<1	4.84	14	562	2	13	0.87	<4	22	171	42	3.89	<0.01	28	1.50	495	<1	152	549	28	0.54	8	13	15	279	2792	<2	87	<10	13	59
212939	1369548	0.007	<1	5.97	15	576	2	6	0.93	<4	22	174	49	4.12	<0.01	33	1.60	552	<1	147	571	34	0.68	8	21	17	251	2996	<2	92	<10	14	64
212940D	1369548	<0.005	<1	4.57	11	537	2	12	0.79	<4	22	164	51	4.01	<0.01	27	1.53	521	<1	151	598	26	0.57	<5	11	13	269	2865	2	89	<10	13	67
212941	1369549	<0.005	<1	5.24	14	581	2	9	0.84	<4	21	157	47	3.82	<0.01	28	1.52	510	<1	146	555	28	0.60	9	10	13	253	2797	2	90	<10	14	62
212942	1369550	0.006	<1	4.62	15	485	2	11	0.88	<4	22	165	46	3.87	0.10	25	1.47	523	<1	154	544	31	0.53	<5	16	15	267	2655	3	83	<10	13	61
212943	1369551	<0.005	<1	3.11	11	522	2	<1	0.76	<4	20	177	44	3.60	0.06	20	1.26	495	3	181	497	30	0.39	<5	18	17	268	2468	<2	71	<10	12	53
212944	1369552	<0.005	<1	3.68	12	473	2	14	0.82	<4	21	165	42	3.85	0.03	23	1.43	519	<1	136	533	29	0.44	6	25	16	267	2673	3	80	<10	13	60
212945	1369553	<0.005	<1	4.56	13	520	2	14	0.92	<4	23	161	48	3.88	0.12	26	1.51	494	<1	143	550	29	0.54	7	17	19	284	2603	2	82	<10	13	57
212946	1369554	0.007	<1	5.08	13	521	2	3	0.96	<4	23	171	49	4.11	<0.01	28	1.58	540	<1	138	577	31	0.59	6	18	14	282	2883	4	87	<10	14	63

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012

Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/25/2012
 Date Completed: 08/14/2012
 Job #: 201242815
 Reference: TL 12 271
 Sample #: 289

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
212947	1369555	0.007	<1	4.51	12	604	2	<1	0.90	<4	22	181	47	3.94	<0.01	25	1.47	528	2	164	556	32	0.56	6	24	15	299	2824	4	81	<10	13	64
212948	1369556	0.010	<1	5.06	11	639	2	13	0.98	<4	23	182	48	4.06	<0.01	28	1.53	546	<1	156	584	29	0.58	7	13	15	314	2996	2	84	<10	13	64
212949	1369557	0.014	<1	4.15	14	609	2	9	0.96	<4	24	193	54	4.30	<0.01	26	1.51	587	<1	166	611	32	0.51	7	13	16	279	3050	<2	88	<10	13	67
212950	1369558	0.005	<1	3.97	15	542	2	9	0.76	<4	22	202	47	4.05	<0.01	22	1.41	531	4	189	516	30	0.60	8	16	17	262	2714	4	81	<10	13	57
212951D	1369558	0.009	<1	3.23	12	539	2	2	0.65	<4	21	177	46	3.92	<0.01	21	1.40	518	<1	147	508	31	0.52	6	20	14	243	2621	<2	80	<10	12	62
212952	1369559	0.015	<1	4.81	15	579	2	11	0.65	<4	26	199	48	4.82	<0.01	27	1.84	614	<1	172	616	30	0.49	6	19	15	237	2985	2	108	<10	15	71
212953	1369560	<0.005	<1	6.64	14	602	2	16	0.88	<4	27	190	53	4.92	0.04	31	1.93	606	<1	142	636	33	0.63	7	18	16	256	3143	4	114	<10	16	70
212954	1369561	0.011	<1	6.23	17	564	3	5	0.73	<4	27	196	50	5.01	0.06	31	1.96	611	<1	167	652	29	0.61	5	11	14	238	3073	4	119	<10	16	76
212955	1369562	0.007	<1	5.74	17	475	2	9	0.83	<4	27	171	50	5.04	0.29	27	1.98	569	<1	142	653	34	0.57	7	11	18	227	3058	<2	118	<10	15	70
212956	1369563	0.005	<1	<0.01	10	<1	<2	8	<0.01	<4	<1	<1	<1	0.02	<0.01	<1	0.06	<100	<1	10	<100	13	0.14	<5	15	12	10	<100	4	<2	<10	<2	<1
212957	1369564	0.011	<1	5.48	16	448	2	13	0.71	<4	25	166	48	4.24	<0.01	23	1.70	535	<1	132	562	26	0.59	5	21	15	213	2733	<2	98	<10	13	62
212958	1369565	0.016	<1	3.62	10	569	2	<1	0.63	<4	23	151	46	4.09	<0.01	21	1.60	471	<1	137	644	24	0.48	6	17	12	274	2637	2	94	<10	12	63
212959	1369566	0.015	<1	6.17	13	679	2	6	0.95	<4	26	167	50	4.55	<0.01	30	1.83	540	<1	141	718	27	0.69	<5	17	19	337	3335	<2	109	<10	14	73
212960	1369567	0.014	<1	4.35	9	446	2	4	0.51	<4	24	163	47	4.26	<0.01	21	1.65	532	<1	129	537	22	0.57	7	15	17	182	2784	<2	97	<10	12	58
212961	1369568	0.013	<1	5.52	16	417	2	12	0.67	<4	26	165	49	4.61	<0.01	23	1.76	525	<1	135	647	32	0.83	5	14	13	169	2972	3	107	<10	14	69
212962D	1369568	0.014	<1	5.12	16	429	2	13	0.66	<4	23	159	44	4.35	<0.01	25	1.70	557	<1	126	533	25	0.74	7	16	13	145	2765	<2	99	<10	14	64
212963	1369569	0.013	<1	4.00	18	344	2	<1	0.49	<4	23	123	65	4.47	<0.01	17	1.26	406	<1	133	680	31	2.47	<5	15	14	242	1495	<2	68	<10	12	262
212964	1369570	0.005	<1	4.34	14	484	2	8	0.61	<4	23	166	47	4.29	<0.01	20	1.65	530	<1	150	554	26	0.64	<5	17	14	195	2706	<2	94	<10	13	66
212965	1369571	0.010	<1	4.15	15	471	2	10	0.46	<4	25	170	51	4.74	<0.01	18	1.66	512	<1	156	531	33	1.03	5	17	14	185	2426	<2	100	<10	14	69
212966	1369572	0.016	<1	5.37	15	434	2	7	0.71	<4	24	156	45	4.14	0.02	21	1.68	499	<1	115	536	30	0.76	6	18	13	221	2627	2	97	<10	14	64

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012

Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/25/2012
 Date Completed: 08/14/2012
 Job #: 201242815
 Reference: TL 12 271
 Sample #: 289

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
212967	1369573	0.016	<1	5.10	15	483	2	3	0.78	<4	23	144	42	4.21	<0.01	22	1.67	488	<1	127	658	26	0.78	5	14	16	265	2557	<2	93	<10	15	69
212968	1369574	0.014	<1	4.06	16	438	2	7	0.55	<4	20	138	37	3.77	<0.01	19	1.53	473	<1	108	524	29	0.54	<5	17	15	225	2419	<2	86	<10	12	57
212969	1369575	0.023	<1	4.16	12	412	2	7	1.07	<4	16	96	38	3.30	<0.01	15	1.33	428	<1	113	692	26	0.47	<5	10	17	321	2264	4	68	<10	13	56
212970	1369576	0.015	<1	4.89	13	425	<2	5	1.15	<4	17	95	36	3.28	<0.01	17	1.33	444	<1	110	691	22	0.57	9	21	14	333	2460	4	69	<10	13	55
212971	1369577	0.018	<1	3.93	16	490	2	5	0.77	<4	21	161	44	3.89	<0.01	19	1.47	534	<1	140	536	31	0.48	<5	14	16	255	2653	<2	84	<10	13	61
212972	1369578	<0.005	<1	4.29	11	601	2	3	0.87	<4	21	181	45	3.86	0.17	20	1.42	523	<1	160	553	34	0.57	<5	20	15	278	2792	<2	80	<10	13	62
212973D	1369578	0.007	<1	4.01	15	576	2	4	0.91	<4	20	166	46	3.62	<0.01	19	1.37	504	<1	136	525	26	0.57	<5	14	15	270	2675	<2	74	<10	12	55
212974	1369579	0.009	<1	4.40	17	630	2	8	0.93	<4	22	168	51	3.94	<0.01	22	1.47	543	<1	133	588	34	0.58	5	14	14	303	2911	<2	82	<10	14	59
212975	1369580	4.856	<1	0.89	10	<1	<2	9	<0.01	<4	<1	<1	2	0.02	1.34	<1	0.10	<100	<1	25	<100	13	0.26	<5	20	13	18	<100	9	<2	<10	2	<1
212976	1369581	<0.005	<1	4.45	16	544	2	6	0.66	<4	21	170	46	3.79	0.11	25	1.43	469	<1	161	530	26	0.56	7	19	15	249	2604	3	81	<10	13	55
212977	1369582	<0.005	<1	4.94	14	495	2	6	0.92	<4	20	172	46	3.76	0.12	28	1.41	510	2	169	546	28	0.64	5	10	18	265	2611	<2	78	<10	13	52
212978	1369583	0.165	<1	7.51	10	606	2	4	1.12	<4	21	162	51	3.81	<0.01	37	1.54	500	<1	145	539	33	0.98	<5	18	18	311	3002	6	86	<10	16	58
212979	1369584	<0.005	<1	6.20	16	549	2	11	1.36	<4	21	138	40	3.86	<0.01	33	1.62	549	<1	130	681	27	0.71	6	17	13	306	3035	6	90	<10	14	58
212980	1369585	<0.005	<1	0.71	9	276	2	1	0.10	<4	11	85	20	1.83	<0.01	7	0.77	215	<1	84	285	18	0.41	<5	11	10	129	1308	<2	39	<10	7	24
212981	1369586	<0.005	<1	1.62	16	409	2	12	0.29	<4	16	147	39	2.91	<0.01	15	1.08	325	4	174	632	29	0.43	<5	18	13	173	1809	<2	56	<10	10	62
212982	1369587	<0.005	<1	3.76	15	543	2	3	0.63	<4	21	165	46	3.79	<0.01	25	1.41	526	<1	154	525	29	0.52	6	16	16	219	2556	<2	81	<10	13	60
212983	1369588	<0.005	<1	3.71	15	537	2	4	0.65	<4	22	188	48	4.00	<0.01	25	1.45	516	5	186	532	31	0.48	5	16	13	223	2567	<2	83	<10	13	63
212984R	1369588	<0.005	<1	4.06	13	525	2	3	0.71	<4	21	182	45	3.91	<0.01	25	1.44	513	3	170	524	28	0.52	5	16	13	231	2600	<2	82	<10	13	57
212985	1369589	0.011	<1	2.91	15	530	2	8	0.49	<4	19	168	41	3.61	<0.01	22	1.41	426	<1	152	477	32	0.40	7	15	17	226	2422	<2	76	<10	11	58
212986	1369590	0.006	<1	5.76	<2	620	2	<1	1.12	5	25	208	52	4.45	0.36	30	1.67	634	8	181	574	27	0.27	<5	<5	<10	379	3393	<2	107	<10	18	66

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012

Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/25/2012
 Date Completed: 08/14/2012
 Job #: 201242815
 Reference: TL 12 271
 Sample #: 289

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
212987	1369591	<0.005	<1	4.81	17	571	2	9	0.75	<4	22	178	56	3.97	<0.01	28	1.50	521	<1	159	553	29	0.57	5	10	16	241	2811	8	86	<10	14	70
212988	1369592	0.009	<1	4.11	17	615	2	31	0.66	<4	23	183	54	4.05	<0.01	27	1.53	482	2	173	564	32	0.50	5	20	24	266	2720	<2	83	<10	13	69
212989	1369593	0.007	<1	3.47	12	551	2	2	0.64	<4	22	162	47	3.87	0.22	23	1.47	503	<1	149	557	35	0.44	5	17	16	253	2615	<2	80	<10	12	60
212990	1369594	0.006	<1	3.70	12	543	2	5	0.54	<4	22	168	46	4.03	0.05	27	1.54	475	<1	152	527	31	0.47	7	21	17	222	2651	<2	85	<10	13	56
212991	1369595	<0.005	<1	4.05	14	490	2	6	1.48	<4	22	99	45	4.18	0.03	25	1.55	546	<1	121	931	29	0.55	<5	10	15	362	2708	<2	89	<10	14	63
212992	1369596	<0.005	<1	3.30	14	535	2	15	0.62	<4	19	136	42	3.46	0.06	23	1.39	432	<1	121	511	25	0.48	<5	15	14	255	2395	<2	69	<10	10	56
212993	1369597	<0.005	<1	2.86	14	507	2	<1	0.58	<4	21	152	44	3.61	<0.01	22	1.32	488	<1	140	508	27	0.43	5	18	15	211	2418	<2	76	<10	11	52
212994	1369598	<0.005	<1	2.84	9	445	2	<1	0.70	<4	21	179	48	3.82	<0.01	22	1.33	578	<1	171	537	27	0.44	8	15	15	221	2480	<2	78	<10	12	57
212995D	1369598	<0.005	<1	4.97	10	487	2	5	0.98	<4	21	181	49	3.90	<0.01	28	1.43	601	<1	156	560	26	0.64	5	16	13	258	2800	2	83	<10	13	58
212996	1369599	0.009	<1	3.78	10	495	2	5	0.60	<4	21	152	41	3.80	<0.01	25	1.51	482	<1	130	499	31	0.46	6	15	13	212	2563	<2	82	<10	13	56
212997	1369600	0.204	<1	<0.01	9	<1	<2	10	<0.01	<4	1	<1	4	0.10	<0.01	<1	0.21	<100	<1	34	<100	13	0.49	<5	22	13	35	193	<2	3	<10	3	2
212998	1369601	<0.005	<1	3.85	13	547	2	7	0.69	<4	19	140	40	3.46	0.06	25	1.36	476	<1	110	511	26	0.52	<5	17	15	234	2579	<2	76	<10	12	54
212999	1369602	0.008	<1	4.46	15	587	2	<1	0.65	<4	21	155	43	3.79	0.16	29	1.48	467	<1	121	545	27	0.54	5	20	13	250	2754	<2	82	<10	13	56
213000	1369603	0.008	<1	4.15	14	530	2	3	0.71	<4	21	161	43	3.82	0.20	28	1.45	487	<1	142	535	28	0.52	<5	18	14	253	2630	<2	80	<10	13	60
213001	1369604	0.009	<1	2.97	12	475	2	14	0.56	<4	19	144	41	3.50	0.31	22	1.33	458	<1	116	521	28	0.43	8	20	14	225	2316	<2	73	<10	12	56
213002	1369605	<0.005	<1	3.62	16	513	2	2	0.76	<4	19	137	41	3.29	0.18	20	1.27	465	<1	107	513	27	0.51	5	18	16	274	2366	<2	70	<10	12	50
213003	1369606	<0.005	<1	3.35	10	491	2	15	0.74	<4	18	134	40	3.27	<0.01	19	1.25	459	<1	111	498	28	0.49	7	13	17	268	2236	<2	69	<10	12	47
213004	1369607	0.007	<1	4.39	15	466	2	2	0.68	<4	20	145	40	3.53	0.16	28	1.43	447	<1	127	496	28	0.55	<5	14	15	246	2466	<2	74	<10	12	52
213005	1369608	0.009	<1	3.66	13	487	<2	4	0.61	<4	21	146	42	3.65	<0.01	21	1.44	490	<1	104	518	27	0.51	5	17	16	215	2519	3	78	<10	13	51
213006D	1369608	<0.005	<1	3.79	11	487	2	4	0.61	<4	21	146	44	3.63	<0.01	22	1.44	492	<1	119	514	28	0.51	<5	9	15	211	2523	3	78	<10	13	56

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012

Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/25/2012
 Date Completed: 08/14/2012
 Job #: 201242815
 Reference: TL 12 271
 Sample #: 289

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
213007	1369609	<0.005	<1	4.65	15	498	2	11	0.77	<4	19	138	40	3.34	0.03	26	1.37	450	<1	119	516	28	0.62	5	17	13	253	2557	4	71	<10	12	49
213008	1369610	<0.005	<1	3.52	11	558	2	4	0.79	<4	19	122	36	3.24	<0.01	23	1.31	471	<1	109	591	26	0.49	<5	18	15	306	2481	2	69	<10	11	52
213009	1369611	0.010	<1	4.76	14	479	2	3	0.73	<4	21	157	40	3.86	<0.01	32	1.54	494	<1	127	533	28	0.56	7	18	17	222	2815	<2	87	34	13	60
213010	1369612	<0.005	<1	3.16	13	480	2	11	0.57	<4	22	153	43	3.86	0.14	26	1.48	483	<1	135	521	21	0.40	8	13	15	218	2485	<2	85	<10	12	56
213011	1369613	<0.005	<1	4.42	19	569	3	2	0.99	<4	22	154	46	3.64	0.24	28	1.63	450	<1	111	672	38	0.58	5	12	18	340	2613	<2	80	<10	13	60
213012	1369614	<0.005	<1	4.91	16	492	2	5	0.88	<4	21	156	41	3.77	0.26	28	1.54	533	<1	135	547	33	0.63	5	16	16	263	2724	<2	83	<10	13	54
213013	1369615	<0.005	<1	4.89	14	518	2	2	0.93	<4	26	158	50	4.50	0.25	31	1.63	572	<1	127	584	33	0.74	6	14	16	224	2847	2	95	<10	14	84
213014	1369616	0.013	<1	5.29	14	449	2	7	1.01	<4	23	147	54	3.95	0.10	27	1.50	530	<1	124	548	35	0.79	<5	18	18	270	2768	<2	82	<10	14	63
213015	1369617	0.010	<1	3.97	13	446	2	<1	0.86	<4	21	148	47	3.83	0.26	26	1.49	497	<1	125	540	30	0.52	6	14	16	247	2604	<2	81	<10	12	57
213016	1369618	<0.005	<1	4.16	12	441	2	13	0.93	<4	20	139	45	3.55	0.28	23	1.43	513	<1	119	527	29	0.55	5	15	15	269	2513	<2	76	<10	12	52
213017D	1369618	<0.005	<1	3.30	12	443	2	12	0.77	<4	21	141	42	3.49	<0.01	20	1.39	512	<1	111	516	25	0.52	<5	16	18	238	2427	<2	76	<10	12	51
213018	1369619	0.006	<1	6.45	<2	583	2	5	1.19	5	22	162	46	4.15	0.35	31	1.74	570	<1	120	565	23	0.25	<5	<5	<10	395	3286	<2	104	<10	18	90
213019	1369620	0.248	<1	<0.01	11	<1	<2	7	<0.01	<4	<1	<1	3	0.05	<0.01	<1	0.16	<100	<1	32	<100	17	0.40	<5	20	16	27	135	<2	2	<10	2	<1
213020	1369621	<0.005	<1	4.07	16	511	2	1	0.67	<4	23	160	48	4.30	<0.01	30	1.69	571	<1	135	561	38	0.49	<5	17	14	192	2854	<2	92	<10	14	81
213021	1369622	<0.005	<1	4.72	20	579	2	20	0.51	<4	23	160	44	4.17	<0.01	28	1.66	596	<1	129	581	26	0.54	10	19	16	190	2842	<2	94	<10	14	47
213022	1369623	0.008	<1	3.47	16	503	2	16	0.38	<4	21	151	59	3.92	<0.01	23	1.55	527	<1	112	602	18	0.45	7	17	15	174	2565	<2	85	12	13	38
213023	1369624	<0.005	<1	4.99	13	381	2	<1	0.50	<4	21	147	46	3.46	<0.01	22	1.44	424	<1	111	571	15	0.63	<5	18	16	168	2529	<2	78	<10	14	30
213024	1369625	<0.005	<1	4.66	12	588	2	3	0.47	<4	21	156	36	3.91	<0.01	29	1.58	471	<1	112	575	17	0.53	6	18	12	159	2632	<2	92	<10	14	30
213025	1369626	<0.005	<1	4.39	10	572	<2	12	0.45	<4	21	152	39	3.88	0.16	28	1.57	466	<1	121	546	9	0.54	7	19	18	154	2605	<2	89	<10	14	30
213026	1369627	<0.005	<1	4.80	15	571	2	5	0.22	<4	26	164	39	4.68	0.15	39	1.91	523	<1	130	591	18	0.56	6	15	15	151	2989	<2	100	<10	14	34

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012

Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/25/2012
 Date Completed: 08/14/2012
 Job #: 201242815
 Reference: TL 12 271
 Sample #: 289

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
213027	1369628	0.009	<1	4.19	14	503	2	4	1.24	<4	24	139	82	3.52	0.24	28	1.47	400	<1	118	526	21	0.64	<5	14	19	154	2505	<2	87	<10	15	21
213028D	1369628	0.007	<1	4.40	14	522	2	7	1.32	<4	26	143	87	3.68	0.30	30	1.52	415	<1	121	546	19	0.64	10	19	19	163	2627	<2	91	<10	15	24
213029	1369629	0.010	<1	4.58	12	429	2	14	0.26	<4	21	152	25	4.36	<0.01	40	1.87	484	<1	114	543	12	0.48	<5	17	16	113	2628	<2	103	<10	15	39
213030	1369630	<0.005	<1	3.84	13	427	2	10	0.38	<4	26	140	67	4.17	<0.01	34	1.73	440	<1	120	505	18	0.58	<5	12	14	115	2384	<2	93	<10	14	52
213031	1369631	<0.005	<1	3.39	14	408	2	10	0.51	<4	20	148	41	3.59	<0.01	28	1.43	513	<1	123	534	39	0.49	5	20	14	226	2351	<2	73	<10	13	86
213032	1369632	0.007	<1	4.91	16	552	2	12	0.75	<4	23	166	46	4.10	<0.01	34	1.60	648	<1	133	575	41	0.55	<5	19	17	259	2915	2	87	<10	14	94
213033	1369633	<0.005	<1	3.68	15	415	2	4	0.45	<4	18	137	40	3.33	<0.01	26	1.48	522	<1	100	513	61	0.66	<5	17	15	197	2540	<2	67	<10	12	88
213034	1369634	<0.005	<1	4.44	16	473	2	6	1.17	<4	19	137	45	3.27	<0.01	27	1.34	548	<1	110	564	42	0.62	<5	21	14	271	2671	<2	71	<10	13	60
213035	1369635	0.007	<1	3.73	11	543	2	6	0.80	<4	20	152	43	3.63	0.01	26	1.53	503	<1	113	541	31	0.52	6	14	14	247	2648	<2	75	<10	13	79
213036	1369636	<0.005	<1	5.18	16	602	2	7	0.93	<4	22	157	44	3.90	0.02	32	1.64	561	<1	132	576	37	0.60	7	17	14	273	2840	2	85	<10	14	67
213037	1369637	<0.005	<1	3.82	12	437	2	10	0.78	<4	19	150	43	3.57	0.22	29	1.47	514	<1	139	522	30	0.49	6	20	18	245	2485	<2	76	<10	13	52
213038	1369638	0.009	<1	4.31	15	509	<2	9	0.78	<4	22	166	45	4.07	0.32	26	1.55	540	<1	148	550	27	0.51	6	15	15	243	2753	<2	88	<10	15	57
213039D	1369638	0.008	<1	3.99	15	480	2	12	0.75	<4	21	159	44	3.95	0.15	24	1.51	521	<1	143	538	32	0.48	5	16	15	241	2640	<2	84	<10	14	58
213040	1369639	0.005	<1	3.73	14	418	3	3	0.78	<4	20	151	44	3.84	0.14	25	1.48	493	<1	130	516	33	0.48	5	20	17	257	2443	4	79	<10	14	60
213041	1369640	0.013	<1	<0.01	11	<1	<2	5	<0.01	<4	<1	<1	4	0.09	<0.01	<1	0.21	<100	<1	29	<100	11	0.51	<5	24	15	36	190	5	2	<10	3	<1
213042	1369641	<0.005	<1	5.07	16	541	2	7	0.76	<4	21	143	45	3.59	<0.01	35	1.51	433	<1	126	500	26	0.66	7	16	13	236	2583	<2	79	<10	14	54
213043	1369642	0.012	<1	3.86	14	487	2	7	0.99	<4	18	143	43	3.35	<0.01	21	1.26	542	<1	111	521	28	0.57	<5	16	14	309	2505	<2	67	<10	12	56
213044	1369643	<0.005	<1	3.40	14	481	2	<1	0.76	<4	20	138	41	3.44	<0.01	25	1.32	499	<1	105	507	28	0.50	6	13	13	247	2477	3	70	<10	12	58
213045	1369644	0.010	<1	3.99	15	557	2	5	0.63	<4	26	168	49	4.54	<0.01	34	1.70	507	<1	147	592	32	0.46	<5	14	13	187	3061	<2	98	<10	15	70
213046	1369645	<0.005	<1	1.66	8	335	<2	<1	0.29	<4	17	177	28	2.69	<0.01	13	1.44	338	<1	104	339	18	0.38	<5	17	13	125	1747	<2	60	<10	9	34

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/25/2012
 Date Completed: 08/14/2012
 Job #: 201242815
 Reference: TL 12 271
 Sample #: 289

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
213047	1369646	0.010	<1	4.75	20	446	2	13	0.62	<4	17	120	37	3.05	<0.01	25	1.25	369	<1	104	427	28	0.64	<5	14	13	189	2398	<2	73	<10	12	79
213048	1369647	0.012	<1	2.58	12	323	<2	<1	0.61	<4	13	96	28	2.30	<0.01	13	0.90	345	<1	83	354	20	0.52	<5	14	11	228	1750	<2	47	<10	9	45
213049	1369648	0.009	<1	1.00	9	374	2	4	0.37	<4	18	129	40	3.28	<0.01	14	1.16	453	<1	109	456	27	0.29	<5	12	12	163	2108	<2	68	<10	10	58
213050R	1369648	0.011	<1	1.52	12	366	<2	3	0.39	<4	20	130	41	3.38	<0.01	16	1.21	445	<1	116	461	20	0.33	<5	14	12	158	2169	<2	72	<10	10	52
213051	1369649	0.013	<1	2.25	13	336	2	6	0.18	<4	20	132	36	3.67	<0.01	18	1.34	386	<1	125	430	20	0.35	<5	13	12	138	2211	<2	83	<10	10	51
213052	1369650	0.012	<1	2.39	16	337	2	4	0.12	<4	21	129	38	3.58	<0.01	18	1.39	359	<1	112	467	24	0.43	<5	10	14	105	2106	<2	84	<10	10	55
213053	1369651	0.010	<1	4.43	12	377	2	4	0.59	<4	20	136	38	3.59	<0.01	22	1.39	428	<1	116	464	22	0.55	<5	19	13	163	2492	<2	85	<10	11	64
213054	1369652	0.014	<1	2.64	8	313	2	6	0.68	<4	14	105	30	2.50	<0.01	13	0.96	406	<1	90	382	26	0.50	<5	14	12	213	1817	<2	55	<10	9	37
213055	1369653	<0.005	<1	1.58	12	364	<2	<1	0.22	<4	17	130	32	3.04	<0.01	13	1.10	353	<1	132	394	23	0.32	5	13	11	145	1852	<2	68	<10	8	43
213056	1369654	0.006	<1	1.18	15	358	<2	5	0.14	<4	21	128	41	3.65	<0.01	18	1.36	405	<1	111	470	23	0.29	<5	11	12	121	2091	<2	78	<10	10	49
213057	1369655	0.020	<1	2.91	13	439	<2	10	0.69	<4	16	114	36	2.83	<0.01	17	1.12	387	<1	93	461	27	0.50	<5	15	13	215	2112	<2	61	<10	10	38
213058	1369656	<0.005	<1	4.00	15	415	2	2	0.68	<4	18	114	35	2.93	<0.01	21	1.15	417	<1	88	439	20	0.60	<5	16	15	204	2257	<2	66	<10	11	41
213059	1369657	0.006	<1	2.52	11	488	2	9	0.52	<4	17	130	41	3.10	<0.01	18	1.15	407	<1	112	483	28	0.47	<5	10	13	216	2212	<2	65	<10	11	48
213060	1369658	<0.005	<1	2.20	12	428	2	4	0.55	<4	18	119	36	2.89	<0.01	16	1.10	403	<1	87	434	27	0.44	6	17	15	211	2121	<2	62	<10	10	45
213061D	1369658	0.027	<1	2.00	13	431	<2	9	0.50	<4	18	120	36	2.95	<0.01	16	1.12	414	<1	85	441	24	0.43	5	17	16	202	2149	<2	62	<10	10	42
213062	1369659	0.017	<1	1.52	12	411	<2	6	0.38	<4	18	122	39	3.11	<0.01	15	1.12	423	<1	103	446	24	0.33	<5	19	14	171	2104	<2	66	<10	10	46
213063	1369660	1.899	<1	<0.01	7	<1	<2	6	<0.01	<4	<1	<1	2	0.04	<0.01	<1	0.06	<100	<1	27	<100	8	0.13	<5	17	13	10	<100	<2	<2	<10	<2	<1
213064	1369661	<0.005	<1	0.47	13	362	<2	2	0.42	<4	14	101	31	2.71	<0.01	9	0.98	369	<1	102	476	25	0.27	<5	11	13	186	1784	<2	56	<10	8	45
213065	1369662	0.008	<1	1.58	11	387	<2	4	0.36	<4	17	113	32	3.03	<0.01	17	1.14	384	<1	94	396	21	0.36	<5	17	11	162	2000	<2	66	<10	9	54
213066	1369663	<0.005	<1	3.39	15	412	<2	2	0.65	<4	17	110	33	2.76	<0.01	18	1.07	385	<1	87	391	22	0.55	6	13	13	214	2064	3	63	<10	10	45

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012

Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/25/2012
 Date Completed: 08/14/2012
 Job #: 201242815
 Reference: TL 12 271
 Sample #: 289

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
213067	1369664	<0.005	<1	2.09	10	382	<2	7	0.21	<4	16	111	31	2.76	<0.01	15	1.14	293	<1	99	368	21	0.39	<5	13	14	160	1819	<2	62	<10	8	39
213068	1369665	<0.005	<1	<0.01	9	280	2	<1	<0.01	<4	15	99	30	2.72	<0.01	8	0.98	336	<1	85	355	20	0.19	<5	15	11	83	1464	<2	58	<10	7	36
213069	1369666	0.009	<1	3.47	11	343	<2	4	0.49	<4	15	112	32	2.70	<0.01	18	1.05	370	<1	104	389	24	0.58	<5	16	13	169	1929	<2	63	<10	10	37
213070	1369667	0.007	<1	0.40	10	273	<2	<1	0.36	<4	16	108	35	2.62	<0.01	9	0.91	361	<1	96	387	22	0.27	<5	<5	16	164	1443	<2	54	<10	8	39
213071	1369668	<0.005	<1	1.39	10	309	2	6	0.22	<4	14	103	28	2.44	<0.01	12	0.99	295	<1	95	363	20	0.38	5	11	12	156	1588	<2	52	<10	7	28
213072D	1369668	0.008	<1	2.41	11	356	2	2	0.35	<4	16	110	31	2.71	<0.01	17	1.13	326	<1	100	399	21	0.45	<5	14	11	176	1865	3	58	<10	8	32
213073	1369669	0.010	<1	1.77	11	363	<2	6	0.48	<4	13	101	30	2.38	<0.01	12	0.95	348	<1	83	368	18	0.43	<5	17	13	189	1692	<2	52	<10	8	32
213074	1369670	0.007	<1	0.92	12	332	<2	3	0.24	<4	13	106	30	2.44	<0.01	11	1.01	293	<1	95	385	21	0.35	<5	16	13	164	1670	<2	50	<10	7	32
213075	1369671	0.008	<1	1.88	11	339	2	5	0.42	<4	15	112	36	2.81	<0.01	14	1.08	371	<1	95	443	22	0.39	<5	13	13	169	1998	<2	60	<10	9	37
213076	1369672	0.007	<1	2.24	15	395	2	10	0.47	<4	15	109	32	2.64	<0.01	16	1.09	343	<1	94	429	19	0.43	<5	16	14	201	1876	<2	58	<10	9	44
213077	1369673	0.007	<1	1.77	13	356	2	3	0.41	<4	15	123	34	2.69	<0.01	12	1.06	335	<1	120	413	27	0.42	5	12	13	187	1771	<2	57	<10	8	37
213078	1369674	0.008	<1	1.87	14	303	<2	8	0.41	<4	16	105	32	2.65	<0.01	12	1.04	338	<1	90	385	19	0.40	<5	13	14	142	1739	<2	62	<10	9	20
213079	1369675	0.008	<1	1.68	10	324	2	7	0.31	<4	15	118	33	2.67	<0.01	11	1.05	305	<1	118	402	20	0.37	<5	14	13	161	1704	<2	61	<10	8	25
213080	1369676	0.013	<1	1.18	10	312	2	3	0.30	<4	13	106	26	2.30	<0.01	9	0.89	295	<1	104	355	23	0.36	<5	16	<10	169	1503	<2	50	<10	8	24
213081	1369677	0.008	<1	1.66	9	314	2	<1	0.27	<4	15	103	31	2.59	<0.01	13	1.01	309	<1	93	382	20	0.39	<5	16	11	147	1683	<2	59	<10	8	31
213082	1369678	0.011	<1	1.50	10	280	<2	<1	0.24	<4	16	100	30	2.68	<0.01	14	1.03	313	<1	84	365	21	0.36	<5	10	14	134	1636	<2	61	<10	9	33
213083D	1369678	0.007	<1	2.24	13	298	2	<1	0.29	<4	15	99	29	2.61	<0.01	16	1.04	298	<1	81	369	20	0.44	5	14	13	136	1701	<2	62	<10	9	33
213084	1369679	<0.005	<1	1.68	10	307	2	12	0.36	<4	16	102	32	2.61	<0.01	16	1.07	316	<1	75	427	21	0.43	6	11	10	153	1778	2	57	<10	9	35
213085	1369680	0.013	<1	<0.01	9	<1	<2	5	<0.01	<4	<1	<1	2	0.08	<0.01	<1	0.13	<100	<1	19	<100	10	0.30	<5	18	11	21	123	<2	2	<10	2	<1
213086	1369681	<0.005	<1	2.48	13	444	2	11	0.28	<4	18	112	35	2.99	<0.01	20	1.15	353	<1	87	420	24	0.43	<5	17	14	146	2039	2	70	<10	10	42

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 28, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/25/2012
 Date Completed: 08/14/2012
 Job #: 201242815
 Reference: TL 12 271
 Sample #: 289

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
213087	1369682	<0.005	<1	1.26	10	372	<2	3	0.37	<4	14	99	29	2.35	<0.01	6	0.90	336	<1	83	377	19	0.38	<5	11	12	187	1711	<2	50	<10	8	36
213088	1369683	<0.005	<1	1.41	14	327	<2	4	0.32	<4	15	96	30	2.48	<0.01	13	1.00	307	<1	72	399	22	0.39	5	12	11	167	1691	2	55	<10	8	35
213089	1369684	<0.005	<1	1.73	11	362	2	4	0.40	<4	15	105	33	2.63	<0.01	14	1.05	324	<1	86	419	28	0.41	5	14	15	187	1745	<2	56	<10	9	65
213090	1369685	0.005	<1	2.17	9	362	<2	2	0.43	<4	15	97	30	2.52	<0.01	14	1.00	338	<1	79	376	22	0.44	5	18	13	173	1714	<2	59	<10	9	41
213091	1369686	<0.005	<1	0.98	10	320	<2	6	0.25	<4	15	106	29	2.45	<0.01	10	0.90	340	<1	83	374	19	0.33	<5	12	11	151	1548	<2	54	<10	8	32
213092	1369687	<0.005	<1	1.11	12	311	<2	6	0.41	<4	13	85	23	2.15	<0.01	9	0.92	286	<1	77	391	19	0.37	<5	17	<10	193	1500	<2	48	<10	7	28
213093	1369688	<0.005	<1	1.71	11	317	<2	3	0.31	<4	15	93	26	2.55	<0.01	11	1.01	303	<1	71	389	21	0.38	<5	13	13	159	1639	<2	58	<10	8	25
213094D	1369688	<0.005	<1	2.64	8	376	<2	5	0.45	<4	17	110	31	2.95	<0.01	16	1.18	349	<1	77	447	20	0.43	<5	17	14	183	1982	<2	68	<10	10	30
213095	1369689	<0.005	<1	2.77	16	351	2	2	0.34	<4	18	119	35	3.18	<0.01	15	1.18	347	<1	103	469	21	0.40	5	14	12	158	1726	<2	74	<10	11	37
213096	1369690	<0.005	<1	2.81	12	333	2	2	0.49	<4	17	105	31	2.73	<0.01	13	1.08	360	<1	89	422	21	0.47	<5	10	13	154	2004	<2	67	<10	9	33
213097	1369691	<0.005	<1	1.90	16	327	<2	7	0.27	<4	19	118	35	3.24	<0.01	12	1.21	388	<1	102	451	23	0.36	<5	13	13	107	2078	<2	78	<10	10	41
213098	1369692	<0.005	<1	1.60	14	267	2	<1	0.36	<4	15	103	31	2.79	<0.01	10	1.05	382	<1	87	413	23	0.38	5	15	13	146	1875	<2	62	<10	9	39
213099	1369693	<0.005	<1	1.60	11	345	2	4	0.49	<4	15	101	31	2.57	<0.01	11	0.96	367	<1	77	378	22	0.39	6	14	12	177	1871	<2	56	<10	9	38
213100	1369694	0.009	<1	1.89	9	350	<2	<1	0.42	<4	14	97	29	2.58	<0.01	14	0.99	344	<1	74	359	20	0.41	<5	13	12	168	1849	<2	57	<10	9	37
213101	1369695	0.005	<1	1.38	11	350	2	3	0.36	<4	14	100	30	2.50	<0.01	11	0.93	323	<1	76	364	20	0.38	<5	17	13	172	1753	<2	55	<10	9	38
213102	1369696	<0.005	<1	2.53	9	373	2	3	0.62	<4	16	115	34	2.70	<0.01	14	1.00	389	<1	89	426	26	0.50	<5	12	13	225	1977	<2	59	<10	10	52
213103	1369697	<0.005	<1	2.23	13	347	2	<1	0.38	<4	14	93	26	2.34	<0.01	12	0.97	298	<1	70	372	25	0.51	<5	12	14	195	1747	<2	51	<10	10	47

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, August 9, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/10/2012
 Date Completed: 07/27/2012
 Job #: 201242629
 Reference: TL 12 272
 Sample #: 115

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
196423	1365186	0.042	1	8.47	12	618	2	4	2.87	7	14	47	92	3.13	0.12	32	1.55	904	<1	61	808	88	1.47	5	<5	<10	389	2879	<2	70	15	11	1084
196424	1365187	0.023	1	5.46	3	469	<2	<1	1.93	<4	11	17	104	2.38	<0.01	18	1.25	746	<1	34	666	126	1.18	5	<5	<10	297	2264	<2	52	<10	8	214
196425	1365188	0.041	1	5.57	9	564	<2	5	1.91	<4	12	15	54	2.68	<0.01	18	1.21	682	<1	34	802	78	1.40	<5	<5	<10	313	2345	3	56	<10	8	168
196426	1365189	0.036	<1	6.10	<2	623	<2	<1	2.14	6	12	19	91	2.56	<0.01	16	1.04	627	<1	43	717	19	1.18	<5	<5	<10	338	2252	2	57	16	8	1160
196427	1365190	<0.005	<1	4.99	4	376	<2	6	2.58	<4	17	49	24	3.44	<0.01	11	1.49	696	<1	32	640	11	0.51	<5	<5	<10	303	3061	<2	117	22	19	62
196428	1365191	0.025	1	5.34	3	498	<2	4	2.01	<4	10	18	44	2.55	<0.01	17	1.12	637	<1	40	700	18	1.28	<5	<5	<10	313	2205	3	53	<10	8	258
196429	1365192	0.013	<1	4.37	6	600	<2	3	1.84	<4	10	17	17	2.44	<0.01	18	1.51	773	<1	43	626	33	1.03	<5	<5	<10	322	2489	5	54	<10	7	156
196430	1365193	0.024	1	4.13	5	587	<2	4	2.02	5	10	24	64	2.85	<0.01	15	1.35	747	<1	49	624	48	1.46	<5	<5	<10	288	2473	<2	53	12	8	991
196431	1365194	0.032	3	4.15	11	450	<2	4	1.85	8	15	20	49	2.94	0.04	14	1.52	916	<1	45	640	1718	1.93	<5	<5	<10	338	2312	8	51	16	8	1674
196432	1365195	0.028	<1	4.14	8	553	<2	<1	1.64	<4	12	17	33	2.63	<0.01	14	1.03	627	<1	38	684	56	1.44	<5	<5	<10	319	2295	<2	55	<10	8	203
196433D	1365195	0.036	<1	2.63	3	481	<2	3	1.30	<4	11	17	31	2.48	<0.01	9	0.96	589	<1	37	648	38	1.28	<5	<5	<10	263	2059	<2	51	<10	7	181
196434	1365196	0.059	1	5.39	11	515	<2	1	1.90	<4	10	23	31	2.45	<0.01	11	0.98	593	<1	52	640	40	1.33	<5	<5	<10	359	2214	7	52	<10	8	178
196435	1365197	0.098	<1	4.35	6	511	<2	10	2.56	<4	10	26	20	2.66	<0.01	15	1.47	727	<1	46	581	11	1.55	6	<5	<10	301	2137	3	48	<10	8	303
196436	1365198	0.062	<1	5.04	11	751	<2	<1	1.82	<4	11	25	29	2.32	<0.01	13	1.01	488	<1	40	592	14	1.26	7	<5	<10	319	2294	<2	53	<10	7	159
196437	1365199	0.065	<1	6.14	7	666	<2	<1	1.69	<4	9	25	20	2.10	<0.01	14	0.95	432	<1	37	570	13	1.51	<5	<5	<10	311	2191	3	49	<10	8	59
196438	1365200	3.880	62	3.15	41	445	<2	<1	1.52	24	15	33	57	3.47	<0.01	7	1.01	547	<1	29	615	653	0.81	55	<5	256	251	2098	2	97	53	16	2082
196439	1365201	0.063	<1	4.17	7	628	<2	4	1.18	<4	9	30	17	1.70	<0.01	11	0.87	370	<1	37	645	11	1.28	<5	<5	<10	275	1995	<2	44	<10	8	83
196440	1365202	0.027	<1	4.86	10	590	<2	7	1.06	<4	9	23	36	1.47	0.05	9	0.70	286	<1	37	484	12	1.06	<5	<5	<10	312	1985	<2	42	<10	6	146
196441	1365203	0.054	<1	6.32	7	611	<2	<1	1.03	<4	4	21	7	1.03	<0.01	14	0.53	170	<1	36	410	16	1.04	<5	<5	<10	540	1613	<2	31	<10	6	292
196442	1365204	0.012	1	6.64	3	478	<2	2	1.66	<4	5	27	6	1.24	<0.01	14	0.68	271	<1	40	405	12	1.08	<5	<5	<10	350	1668	<2	36	<10	6	56

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, August 9, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/10/2012
 Date Completed: 07/27/2012
 Job #: 201242629
 Reference: TL 12 272
 Sample #: 115

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
196443	1365205	0.014	1	6.39	12	615	<2	<1	1.10	<4	4	19	3	1.19	<0.01	14	0.57	191	<1	30	407	24	1.14	5	<5	<10	296	1697	3	30	10	6	214
196444D	1365205	0.008	<1	6.42	12	622	<2	<1	1.09	<4	4	18	3	1.20	0.23	15	0.57	193	<1	33	402	18	1.13	<5	<5	<10	294	1703	<2	31	<10	6	216
196445	1365206	0.022	1	6.06	15	516	<2	8	1.73	<4	5	16	8	1.35	1.68	12	0.70	302	<1	32	447	25	1.01	<5	<5	<10	315	1664	5	35	10	7	123
196446	1365207	0.022	1	5.77	6	540	<2	2	2.44	4	9	14	44	2.28	0.90	18	1.31	596	<1	32	583	33	1.38	<5	<5	<10	390	2036	4	44	10	8	815
196447	1365208	0.011	1	5.62	11	624	<2	7	2.40	<4	10	11	22	2.15	2.20	20	1.31	579	<1	36	583	30	0.92	<5	<5	<10	403	2345	<2	48	10	8	197
196448	1365209	0.017	1	5.17	5	612	<2	3	1.94	<4	10	26	39	2.13	0.31	20	1.23	538	<1	35	568	32	0.99	6	<5	<10	352	2315	3	49	11	8	438
196449	1365210	0.009	<1	3.21	9	343	<2	3	2.27	<4	14	44	22	3.17	<0.01	7	1.32	630	<1	28	573	6	0.40	<5	<5	<10	278	2682	<2	108	22	16	52
196450	1365211	0.034	<1	2.29	5	392	<2	<1	1.59	<4	8	20	34	1.98	<0.01	13	1.12	490	<1	54	463	19	1.13	<5	<5	<10	297	1803	<2	42	10	6	723
196451	1365212	0.680	2	3.84	13	441	5	6	1.60	8	14	26	85	2.28	0.07	13	1.15	496	<1	34	491	19	1.43	<5	<5	<10	313	1910	<2	48	<10	12	819
196452	1365213	0.014	<1	5.07	5	492	<2	5	1.71	<4	9	28	39	1.97	0.12	14	0.86	375	<1	41	509	14	0.75	<5	<5	<10	340	2019	<2	46	<10	8	92
196453	1365214	0.025	<1	5.32	19	567	<2	2	2.82	<4	8	14	8	1.87	<0.01	15	1.50	759	<1	31	536	22	1.21	<5	<5	<10	231	1843	<2	39	<10	8	87
196454	1365215	0.021	<1	5.07	8	414	<2	<1	1.22	<4	5	13	7	0.55	<0.01	11	0.68	184	<1	30	405	9	0.50	<5	<5	<10	154	1438	<2	28	<10	5	41
196455D	1365215	0.023	<1	4.36	6	382	<2	<1	1.03	<4	5	15	7	0.52	<0.01	10	0.64	166	<1	32	380	8	0.46	<5	<5	<10	140	1360	<2	27	<10	5	35
196456	1365216	0.018	<1	1.90	9	277	<2	<1	0.75	<4	4	8	8	0.42	<0.01	3	0.51	139	<1	24	327	9	0.36	<5	<5	<10	106	1093	<2	22	<10	4	44
196457	1365217	0.025	<1	3.92	11	398	<2	<1	1.19	<4	7	23	14	0.57	0.26	9	0.75	209	<1	51	416	18	0.48	5	<5	<10	138	1432	5	30	<10	5	58
196458	1365218	0.102	2	3.27	31	413	<2	<1	0.45	<4	7	29	36	0.88	0.14	5	0.62	326	<1	61	351	198	0.94	<5	<5	<10	102	1317	<2	25	<10	5	461
196459	1365219	0.032	<1	3.90	14	320	<2	<1	1.46	<4	6	22	7	0.73	0.17	7	0.70	297	<1	35	378	45	0.75	<5	<5	<10	134	1349	2	27	<10	5	59
196460	1365220	1.742	<1	1.58	3	298	<2	<1	1.79	<4	14	37	26	2.99	<0.01	2	1.19	579	<1	28	521	6	0.31	<5	<5	<10	221	2170	<2	97	17	14	49
196461	1365221	0.023	<1	3.05	12	268	<2	2	1.46	<4	5	18	3	0.65	<0.01	6	0.62	241	<1	35	346	13	0.48	<5	<5	<10	136	1278	<2	26	<10	5	33
196462	1365222	0.015	<1	2.13	9	318	<2	3	0.75	<4	5	29	8	0.93	<0.01	7	0.70	275	<1	54	378	17	0.58	<5	<5	<10	126	1277	2	27	<10	5	35

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, August 9, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/10/2012
 Date Completed: 07/27/2012
 Job #: 201242629
 Reference: TL 12 272
 Sample #: 115

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
196463	1365223	0.027	<1	4.95	8	435	<2	<1	1.23	<4	4	17	11	1.07	<0.01	14	0.78	300	<1	25	377	22	0.82	<5	<5	<10	169	1511	<2	31	<10	6	35
196464	1365224	0.033	<1	4.72	8	391	<2	2	1.65	<4	10	54	23	1.97	<0.01	14	0.88	420	<1	46	408	14	0.98	<5	<5	<10	177	1786	<2	48	<10	9	43
196465	1365225	0.020	<1	4.53	14	403	<2	<1	1.60	<4	10	41	18	1.61	<0.01	12	0.93	369	<1	38	424	16	0.92	<5	<5	<10	163	1683	<2	41	<10	8	33
196466D	1365225	0.018	1	5.45	8	410	<2	4	1.75	<4	8	41	17	1.57	<0.01	15	0.92	367	<1	36	419	14	0.97	<5	5	<10	174	1620	<2	42	<10	9	34
196467	1365226	0.012	<1	4.73	12	346	<2	<1	1.02	<4	5	15	4	0.60	<0.01	11	0.71	265	<1	27	341	14	0.59	<5	<5	<10	140	1316	<2	25	<10	6	45
196468	1365227	0.010	<1	5.52	12	332	<2	3	1.36	<4	3	15	3	0.59	<0.01	15	0.76	225	<1	26	360	15	0.67	<5	<5	<10	152	1530	2	27	<10	5	28
196469	1365228	0.008	1	6.95	16	328	<2	4	2.26	<4	5	33	4	0.97	0.07	21	1.26	492	1	51	404	17	0.81	5	<5	<10	177	1704	<2	31	<10	6	34
196470	1365229	0.016	<1	3.63	3	256	<2	<1	1.85	<4	4	21	11	0.83	<0.01	14	1.00	447	<1	31	311	26	0.58	<5	<5	<10	144	1208	<2	23	<10	5	59
196471	1365230	0.008	1	3.68	4	336	<2	10	2.27	<4	14	42	20	2.98	<0.01	8	1.30	611	<1	28	554	4	0.44	<5	<5	<10	271	2566	<2	102	19	15	50
196472	1365231	0.005	1	4.98	4	402	<2	<1	1.95	<4	6	26	5	0.99	0.02	19	1.12	514	<1	44	395	110	0.51	5	<5	<10	159	1676	<2	32	<10	6	97
196473	1365232	0.012	<1	4.64	10	429	<2	1	2.03	<4	4	24	3	0.68	0.23	16	0.78	282	<1	41	381	28	0.63	<5	<5	<10	173	1626	<2	30	<10	4	36
196474	1365233	0.013	<1	3.65	6	308	<2	4	1.38	<4	3	31	9	0.79	<0.01	11	0.73	234	<1	62	373	15	0.57	<5	<5	<10	130	1445	<2	28	<10	5	27
196475	1365234	0.009	<1	6.12	9	403	<2	<1	1.41	<4	3	23	4	0.77	<0.01	18	0.88	290	<1	40	393	15	0.68	<5	<5	<10	153	1621	2	29	<10	6	22
196476	1365235	0.013	<1	5.76	13	407	<2	4	1.49	<4	2	25	3	0.85	<0.01	18	0.94	390	<1	45	358	33	0.80	<5	<5	<10	157	1545	<2	27	<10	6	30
196477D	1365235	0.016	1	6.10	13	437	<2	4	1.56	<4	3	26	3	0.91	<0.01	18	1.00	421	1	46	380	38	0.78	<5	<5	<10	161	1596	<2	29	<10	6	35
196478	1365236	0.007	1	7.31	16	467	<2	2	1.75	<4	4	33	5	0.99	<0.01	23	1.10	462	3	61	415	45	0.86	6	<5	<10	175	1745	6	32	<10	7	58
196479	1365237	0.015	1	5.81	13	413	<2	<1	1.52	<4	3	37	6	0.88	<0.01	19	1.00	415	3	64	381	39	0.70	<5	<5	<10	159	1532	4	28	<10	6	44
196480	1365238	0.021	<1	5.42	13	493	<2	<1	1.53	<4	5	23	8	0.93	<0.01	16	0.83	267	<1	39	388	20	0.81	<5	<5	<10	154	1571	<2	30	<10	6	23
196481	1365239	0.018	<1	5.79	6	482	<2	<1	2.44	<4	6	15	12	1.55	<0.01	16	0.95	374	<1	28	459	10	1.03	<5	<5	<10	177	1601	3	37	<10	7	44
196482	1365240	0.250	<1	<0.01	296	>5000	<2	2	0.56	<4	2	5	21	1.99	<0.01	<1	0.23	<100	2	11	<100	13	0.66	14	<5	<10	97	610	4	11	32	7	13

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, August 9, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/10/2012
 Date Completed: 07/27/2012
 Job #: 201242629
 Reference: TL 12 272
 Sample #: 115

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
196483	1365241	0.020	1	3.99	32	792	<2	2	2.16	<4	7	22	21	1.80	<0.01	14	1.12	537	<1	33	415	20	1.03	<5	<5	<10	156	1822	3	36	<10	6	164
196484	1365242	0.017	1	4.48	21	560	<2	<1	1.53	<4	5	20	8	1.10	0.07	18	0.88	356	<1	35	404	19	0.88	<5	<5	<10	158	1884	<2	33	<10	5	38
196485	1365243	0.018	1	5.24	15	490	<2	<1	1.79	<4	4	19	7	1.15	0.26	19	1.11	422	<1	30	398	18	0.84	<5	<5	<10	164	1805	<2	31	<10	6	36
196486	1365244	0.073	<1	4.11	22	381	<2	4	1.26	<4	3	17	12	1.46	<0.01	12	0.88	351	<1	30	376	26	1.02	5	<5	<10	129	1583	<2	27	<10	5	56
196487	1365245	0.014	1	7.60	12	509	<2	<1	2.04	<4	4	25	10	1.39	<0.01	23	1.12	413	<1	38	386	27	1.00	<5	<5	<10	185	1809	<2	32	<10	7	84
196488R	1365245	0.029	1	7.30	15	472	<2	8	1.92	<4	3	21	9	1.25	<0.01	21	1.04	375	<1	35	369	25	0.93	<5	<5	<10	179	1723	<2	30	<10	7	62
196489	1365246	0.095	1	3.88	13	353	<2	<1	1.31	<4	4	16	65	1.32	<0.01	13	0.98	419	<1	27	367	70	0.95	<5	<5	<10	130	1497	<2	27	<10	5	351
196490	1365247	0.024	<1	6.12	15	417	<2	15	1.80	<4	3	31	10	1.46	<0.01	16	0.93	347	<1	51	353	17	1.11	<5	<5	<10	167	1466	<2	28	<10	7	48
196491	1365248	0.045	1	7.02	15	493	<2	7	2.22	<4	8	46	18	1.66	0.05	22	1.38	606	<1	46	479	49	0.96	<5	<5	<10	244	1943	7	39	<10	9	115
196492	1365249	0.082	1	6.03	25	587	<2	4	1.46	<4	7	27	22	2.01	<0.01	18	0.87	620	<1	43	677	55	1.90	<5	<5	<10	224	2080	3	43	<10	9	75
196493	1365250	0.005	<1	5.13	2	408	<2	<1	2.64	<4	17	50	24	3.50	0.06	12	1.47	708	<1	33	647	7	0.55	<5	<5	<10	319	3149	<2	119	24	18	61
196494	1365251	0.235	1	5.57	22	569	<2	5	1.61	<4	8	22	18	2.25	0.06	18	0.91	688	<1	35	628	104	2.16	<5	<5	<10	223	2161	<2	44	<10	8	391
196495	1365252	0.058	1	4.94	21	510	<2	8	1.83	<4	7	21	17	1.91	0.11	18	0.95	735	<1	32	535	45	1.79	<5	<5	<10	225	2032	2	40	<10	6	138
196496	1365253	0.177	1	3.99	32	531	2	4	1.42	<4	6	26	18	2.04	0.04	16	0.85	797	<1	41	513	107	2.28	5	<5	<10	221	1970	<2	39	<10	5	142
196497	1365254	0.985	3	4.80	34	546	2	2	1.29	5	7	17	36	1.82	0.03	15	0.84	643	<1	29	525	1010	2.15	8	<5	<10	209	2069	4	39	19	6	1371
196498	1365255	0.210	2	4.00	23	353	<2	<1	2.30	<4	5	21	26	1.26	0.07	15	1.06	1074	<1	37	413	182	1.22	<5	<5	<10	214	1605	<2	29	<10	5	356
196499D	1365255	0.327	1	5.67	23	327	<2	5	2.32	<4	5	19	27	1.26	<0.01	13	1.27	1084	<1	33	446	158	1.16	5	<5	<10	203	1536	3	28	<10	7	331
196500	1365256	0.221	1	6.56	46	374	<2	9	2.57	<4	8	24	39	1.52	<0.01	15	1.42	1070	<1	47	583	166	1.36	<5	<5	<10	220	2009	5	33	<10	8	298
196501	1365257	0.008	1	7.55	14	382	2	8	1.98	<4	8	17	4	1.04	<0.01	21	1.21	673	<1	37	412	92	0.92	<5	<5	<10	234	1651	<2	30	<10	7	126
196502	1365258	0.026	<1	5.64	22	271	<2	3	1.70	<4	12	30	5	1.06	<0.01	16	1.11	643	<1	44	405	61	0.77	7	<5	<10	215	1515	<2	31	<10	6	159

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, August 9, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/10/2012
 Date Completed: 07/27/2012
 Job #: 201242629
 Reference: TL 12 272
 Sample #: 115

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
196503	1365259	0.014	1	7.54	16	349	<2	<1	1.68	5	6	20	8	1.15	<0.01	24	0.99	517	<1	33	417	39	1.02	<5	<5	<10	221	1770	<2	31	<10	7	423
196504	1365260	4.992	60	3.75	44	417	<2	<1	1.55	23	14	32	59	3.61	<0.01	9	1.00	539	<1	28	609	624	0.82	63	<5	244	267	2070	3	99	51	16	2000
196505	1365261	0.013	1	5.16	22	371	<2	5	1.37	<4	6	21	24	1.09	<0.01	13	0.73	416	<1	41	404	47	0.67	8	<5	<10	191	1659	<2	32	<10	5	133
196506	1365262	0.029	<1	4.28	17	330	<2	11	1.26	<4	4	19	18	0.92	<0.01	9	0.55	321	<1	33	397	62	0.65	5	<5	<10	169	1467	2	29	<10	5	100
196507	1365263	0.015	<1	4.67	8	324	<2	<1	1.46	<4	4	22	16	0.88	<0.01	9	0.57	343	<1	32	407	34	0.58	6	<5	<10	172	1495	3	33	<10	5	78
196508	1365264	0.096	1	4.60	11	260	<2	<1	2.04	<4	7	32	40	1.32	<0.01	13	0.80	852	<1	41	520	121	1.00	5	<5	<10	177	1712	3	39	<10	8	451
196509	1365265	0.116	4	4.79	22	360	<2	4	1.48	<4	10	38	25	1.91	<0.01	12	0.74	528	<1	41	431	565	1.38	6	<5	<10	166	1845	<2	44	<10	8	183
196510D	1365265	0.140	4	4.61	18	367	<2	1	1.40	<4	11	41	27	2.05	<0.01	13	0.78	544	<1	45	455	626	1.48	<5	<5	<10	159	1946	2	46	<10	9	183
196511	1365266	<0.005	1	3.73	9	280	<2	<1	1.21	<4	10	27	13	0.76	<0.01	8	0.49	285	<1	35	412	32	0.52	<5	<5	<10	127	1482	<2	35	<10	6	38
196512	1365267	0.027	<1	3.82	11	282	<2	3	1.30	<4	7	29	15	1.40	<0.01	9	0.62	418	<1	38	420	12	0.87	<5	<5	<10	134	1668	<2	38	<10	7	58
196513	1365268	0.015	<1	4.24	10	335	<2	<1	1.11	<4	4	24	14	0.69	<0.01	8	0.62	324	<1	37	407	19	0.48	5	<5	<10	127	1605	<2	31	<10	5	38
196514	1365269	1.160	3	3.07	41	265	<2	11	0.18	9	7	34	232	2.31	<0.01	6	0.40	132	<1	57	380	356	2.90	6	<5	<10	88	1428	2	28	20	5	2106
196515	1365270	0.075	<1	2.63	4	312	<2	<1	2.20	<4	15	46	29	3.32	<0.01	6	1.36	637	<1	30	597	12	0.42	<5	<5	<10	252	2601	3	109	16	16	98
196516	1365271	<0.005	1	4.30	16	297	<2	<1	1.70	<4	9	24	31	0.91	<0.01	6	0.79	560	<1	49	422	102	0.55	5	<5	<10	156	1618	<2	30	10	5	255
196517	1365272	0.009	<1	4.96	15	256	<2	<1	2.26	<4	4	20	4	1.22	<0.01	8	0.78	543	<1	42	458	23	0.89	<5	<5	<10	184	1547	<2	30	<10	5	58
196518	1365273	0.006	1	7.14	15	306	<2	8	2.57	<4	5	32	8	1.88	0.35	21	1.42	839	<1	54	579	17	1.10	5	<5	<10	215	1830	<2	40	<10	7	117
196519	1365274	0.011	2	2.57	11	894	<2	3	3.10	<4	18	52	26	2.89	<0.01	12	1.86	509	<1	99	1890	26	1.40	<5	<5	<10	914	2604	4	62	<10	16	69
196520	1365275	<0.005	<1	2.20	19	402	<2	3	0.85	<4	8	17	10	1.21	<0.01	6	0.43	177	<1	43	521	13	1.24	<5	<5	<10	205	1363	<2	29	<10	6	18
196521D	1365275	<0.005	<1	3.28	28	427	<2	3	0.93	<4	8	17	9	1.15	<0.01	8	0.39	167	<1	45	492	12	1.26	<5	<5	<10	214	1337	<2	29	<10	6	19
196522	1365276	<0.005	<1	2.03	22	335	<2	3	0.85	<4	6	21	13	1.15	<0.01	3	0.35	193	<1	52	407	9	1.20	<5	<5	<10	185	1136	<2	26	<10	5	14

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, August 9, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/10/2012
 Date Completed: 07/27/2012
 Job #: 201242629
 Reference: TL 12 272
 Sample #: 115

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
196523	1365277	<0.005	<1	2.27	19	444	<2	2	0.57	<4	6	18	3	1.47	<0.01	5	0.37	182	<1	39	377	12	1.63	<5	<5	<10	181	1253	<2	25	<10	5	14
196524	1365278	0.009	<1	3.44	23	545	<2	4	1.28	<4	10	49	24	2.35	<0.01	14	0.92	409	<1	61	587	8	2.04	<5	<5	<10	237	1713	<2	47	<10	9	48
196525	1365279	0.005	<1	3.45	24	618	<2	<1	1.36	<4	7	19	22	1.94	<0.01	12	0.87	398	<1	43	645	11	1.44	<5	<5	<10	236	1375	4	40	<10	7	52
196526	1365280	1.904	<1	3.70	8	389	<2	2	2.38	<4	19	51	35	3.82	<0.01	10	1.51	734	<1	36	674	11	0.48	<5	<5	<10	268	2790	<2	121	23	17	66
196527	1365281	0.008	<1	2.78	17	463	<2	4	0.94	<4	7	25	8	1.90	<0.01	8	0.76	340	<1	52	613	16	1.38	5	<5	<10	251	1298	2	40	<10	7	52
196528	1365282	0.039	2	7.09	16	582	2	9	1.30	5	18	90	99	4.64	<0.01	21	0.96	361	<1	110	695	20	3.12	<5	<5	<10	413	1864	<2	79	10	13	77
196529	1365283	0.014	1	7.82	19	574	2	1	2.09	<4	9	37	11	2.40	<0.01	27	1.04	390	<1	58	655	17	2.11	<5	<5	<10	448	2069	<2	51	<10	9	41
196530	1365284	0.012	1	7.46	23	486	2	11	2.52	<4	7	18	11	2.21	<0.01	31	1.22	412	<1	39	662	18	1.88	<5	<5	<10	470	1901	<2	44	<10	8	46
196531	1365285	0.011	<1	6.17	9	549	<2	6	2.86	<4	8	18	9	2.40	<0.01	23	1.23	441	<1	43	710	15	1.13	<5	<5	<10	498	2116	<2	46	<10	7	45
196532D	1365285	0.010	1	7.89	8	526	2	4	2.93	<4	8	21	9	2.29	<0.01	34	1.26	425	<1	43	693	14	1.34	8	<5	<10	489	2152	4	46	<10	8	43
196533	1365286	0.030	2	7.18	12	484	2	<1	3.09	4	23	143	71	4.11	<0.01	32	1.63	624	2	94	567	19	2.64	<5	<5	<10	532	2542	<2	93	<10	14	86
196534	1365287	0.020	2	6.64	8	340	2	15	2.20	4	21	138	109	3.94	<0.01	30	1.78	570	<1	82	533	20	1.91	<5	<5	<10	380	2322	8	80	<10	14	126
196535	1365288	0.034	2	6.19	25	483	2	2	1.84	4	22	148	48	4.03	<0.01	25	1.39	501	<1	94	580	19	2.96	<5	<5	<10	369	2407	<2	99	<10	14	73
196536	1365289	0.015	2	6.44	36	490	<2	2	2.41	<4	19	117	26	3.69	<0.01	34	1.26	556	<1	85	590	19	3.39	<5	<5	<10	381	2206	<2	80	<10	13	72
196537	1365290	<0.005	<1	5.36	8	388	<2	2	2.69	<4	16	51	25	3.57	<0.01	13	1.54	709	<1	35	653	7	0.54	<5	<5	<10	314	3075	2	121	22	19	56
196538	1365291	2.758	248	4.03	6	236	<2	4	2.06	<4	8	26	138	2.21	<0.01	10	1.08	957	<1	47	521	1083	1.15	<5	<5	<10	116	1738	<2	33	<10	7	332
196539	1365292	0.043	9	3.37	13	218	<2	<1	1.55	<4	9	25	16	1.55	<0.01	10	0.90	691	<1	47	542	115	0.75	<5	<5	<10	92	1631	<2	31	<10	6	199
196540	1365293	0.020	2	4.85	22	486	<2	<1	2.67	<4	9	29	12	2.00	<0.01	13	1.50	1065	<1	51	577	81	0.74	<5	<5	<10	110	2332	2	44	<10	6	157
196541	1365294	0.199	8	4.29	21	546	<2	<1	1.07	<4	9	32	6	1.79	<0.01	8	0.73	445	<1	60	539	81	1.26	<5	<5	<10	95	2308	<2	47	10	6	103
196542	1365295	0.829	100	3.86	42	461	<2	4	0.35	20	12	29	73	2.43	<0.01	6	0.46	281	<1	49	489	1060	2.60	18	<5	<10	67	2133	<2	41	47	6	4787

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, August 9, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/10/2012
 Date Completed: 07/27/2012
 Job #: 201242629
 Reference: TL 12 272
 Sample #: 115

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
196543D	1365295	0.874	126	3.41	44	451	<2	3	0.28	20	11	26	72	2.38	<0.01	3	0.44	275	<1	47	489	1064	2.51	17	<5	<10	62	2097	2	40	43	6	4722
196544	1365296	0.581	67	2.55	33	432	2	<1	0.18	12	9	13	42	1.69	<0.01	1	0.35	204	<1	31	457	403	1.68	9	<5	<10	53	1926	<2	37	26	6	2526
196545	1365297	0.518	168	2.24	37	354	<2	<1	0.30	7	7	20	52	1.40	<0.01	<1	0.35	201	<1	43	495	2472	1.39	19	<5	<10	58	1571	<2	30	19	6	1544
196546	1365298	0.045	5	3.03	11	264	<2	<1	1.91	<4	6	16	24	1.51	<0.01	9	1.01	715	<1	30	473	122	0.76	<5	<5	<10	96	1597	4	30	<10	6	204
196547	1365299	0.123	3	3.79	19	343	<2	<1	2.03	<4	7	28	19	1.79	<0.01	11	1.08	676	<1	55	554	56	1.07	5	<5	<10	104	1748	<2	32	13	7	456
196548	1365300	0.239	<1	<0.01	<2	<1	<2	<1	<0.01	<4	<1	<1	<1	0.07	<0.01	<1	0.16	<100	<1	4	<100	2	0.32	<5	<5	<10	28	151	<2	2	<10	3	8

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/04/2012
 Date Completed: 07/18/2012
 Job #: 201242544
 Reference: TL 12 273
 Sample #: 118

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
190121	1361468	0.035	<1	1.11	36	293	<2	9	1.15	<4	13	83	26	1.79	<0.01	6	0.72	447	<1	58	353	17	0.73	<5	<5	<10	172	1296	<2	37	<10	6	74
190122	1361469	0.007	<1	1.24	7	370	<2	5	0.53	<4	6	15	7	0.62	<0.01	<1	0.29	159	<1	24	273	5	0.36	<5	<5	<10	155	845	<2	15	<10	3	10
190123	1361470	0.006	<1	0.67	4	262	<2	14	1.24	<4	11	30	18	2.25	<0.01	<1	0.87	455	<1	18	415	2	0.20	<5	<5	<10	168	1670	2	75	11	12	25
190124	1361471	0.007	<1	1.02	8	344	<2	3	0.18	<4	6	12	7	0.75	<0.01	<1	0.34	124	<1	22	254	8	0.46	<5	<5	<10	107	966	<2	19	<10	4	8
190125	1361472	0.011	<1	0.71	5	375	<2	5	0.17	<4	4	21	17	0.68	<0.01	2	0.37	182	<1	36	271	7	0.26	<5	<5	<10	106	960	<2	16	<10	3	18
190126	1361473	0.018	<1	1.56	3	408	<2	10	1.09	<4	4	18	8	1.05	<0.01	2	0.44	317	<1	37	240	6	0.49	<5	5	<10	155	767	<2	12	<10	4	24
190127	1361474	0.063	<1	1.59	6	277	<2	6	0.90	<4	13	85	21	2.47	<0.01	7	1.20	530	<1	60	323	15	0.98	<5	<5	<10	116	1231	<2	52	<10	8	136
190128	1361475	0.025	<1	1.48	5	248	<2	<1	0.53	<4	5	24	11	0.70	<0.01	3	0.62	204	<1	36	238	9	0.33	<5	<5	<10	97	875	2	17	<10	4	13
190129	1361476	0.022	<1	1.00	3	257	<2	11	0.40	<4	3	18	11	0.52	<0.01	2	0.53	174	<1	33	233	7	0.23	<5	<5	<10	86	802	<2	13	<10	4	4
190130	1361477	0.027	<1	0.42	4	155	<2	7	<0.01	<4	3	20	65	0.24	<0.01	<1	0.26	<100	<1	17	142	21	0.16	<5	<5	<10	48	471	<2	6	<10	2	17
190131D	1361477	0.021	<1	0.59	4	144	<2	4	0.11	<4	2	7	7	0.19	<0.01	<1	0.18	<100	<1	14	121	19	0.14	<5	<5	<10	46	437	<2	5	<10	2	7
190132	1361478	0.026	<1	1.62	12	357	<2	5	0.63	<4	5	15	9	0.67	<0.01	3	0.65	209	<1	22	261	22	0.44	<5	<5	<10	121	943	3	14	<10	3	53
190133	1361479	0.046	<1	1.10	5	358	<2	1	0.32	<4	2	10	16	0.54	<0.01	1	0.35	104	<1	19	247	9	0.33	<5	5	<10	110	906	<2	12	<10	3	15
190134	1361480	1.780	<1	2.82	12	356	<2	8	1.87	<4	17	45	36	3.58	<0.01	8	1.34	663	<1	28	590	6	0.28	<5	<5	<10	217	2597	3	112	12	17	41
190135	1361481	0.013	<1	3.69	9	515	<2	14	1.07	<4	5	33	11	0.96	<0.01	9	0.49	164	<1	51	394	5	0.45	<5	<5	<10	146	1491	3	27	<10	5	6
190136	1361482	0.007	<1	3.97	14	449	<2	14	1.66	<4	4	21	11	0.74	<0.01	10	0.59	195	<1	32	368	7	0.45	<5	<5	<10	185	1267	2	21	<10	5	4
190137	1361483	0.276	<1	4.93	23	467	<2	10	0.80	<4	8	36	41	1.34	<0.01	17	0.81	622	<1	56	425	259	0.88	<5	5	<10	134	1717	<2	28	<10	6	501
190138	1361484	5.974	31	2.75	48	266	<2	13	0.62	45	13	33	121	3.32	<0.01	9	0.73	719	<1	60	326	8554	3.65	18	<5	<10	112	1212	<2	19	95	5	12870
190139	1361485	0.146	<1	4.99	36	438	<2	4	0.89	<4	14	65	42	1.74	<0.01	16	0.86	563	<1	60	452	235	1.24	<5	7	<10	134	1983	7	46	<10	9	479
190140	1361486	0.058	<1	5.25	37	468	<2	14	1.02	<4	10	31	21	1.71	<0.01	16	0.77	524	<1	47	617	47	1.16	<5	6	<10	148	1843	4	35	<10	8	67

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/04/2012
 Date Completed: 07/18/2012
 Job #: 201242544
 Reference: TL 12 273
 Sample #: 118

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
190141	1361487	0.020	<1	3.27	15	379	<2	6	0.43	<4	5	32	16	0.88	<0.01	11	0.56	459	<1	44	389	30	0.51	<5	<5	<10	102	1339	<2	25	<10	6	99
190142D	1361487	0.036	<1	4.18	13	413	<2	17	0.59	<4	5	32	17	0.89	<0.01	13	0.60	489	<1	42	403	26	0.53	<5	<5	<10	117	1523	3	27	<10	6	104
190143	1361488	0.040	<1	4.49	15	442	<2	17	0.58	<4	7	40	16	0.97	<0.01	15	0.65	435	<1	59	439	37	0.56	<5	<5	<10	120	1569	3	29	<10	6	70
190144	1361489	0.164	<1	5.24	26	488	<2	7	0.30	<4	10	23	27	1.01	<0.01	14	0.61	402	<1	41	412	273	0.70	<5	7	<10	121	1766	<2	25	<10	5	458
190145	1361490	<0.005	<1	2.69	9	332	<2	20	1.89	<4	18	47	26	3.32	<0.01	8	1.21	656	<1	27	601	11	0.30	<5	<5	<10	230	2657	3	109	16	17	50
190146	1361491	0.054	<1	4.40	15	235	<2	5	2.65	<4	6	28	22	1.72	<0.01	10	1.37	1211	<1	40	406	44	0.93	<5	<5	<10	180	1333	4	23	<10	7	140
190147	1361492	0.026	<1	3.17	3	254	<2	3	1.21	<4	5	28	34	1.41	<0.01	12	0.79	642	<1	42	352	41	0.52	<5	<5	<10	132	1393	3	23	<10	6	79
190148	1361493	0.548	42	3.67	8	228	<2	5	1.07	<4	6	30	24	1.14	<0.01	16	0.83	792	<1	49	360	119	0.50	<5	5	<10	136	1288	2	21	<10	6	166
190149	1361494	0.006	<1	4.05	13	264	<2	21	1.37	<4	8	38	9	1.29	<0.01	15	0.80	634	<1	48	413	17	0.58	<5	5	<10	165	1468	2	28	<10	6	30
190150	1361495	0.010	<1	4.00	7	251	<2	15	1.04	<4	4	15	10	0.75	<0.01	11	0.45	236	<1	26	363	31	0.61	<5	8	<10	179	1188	2	21	<10	5	23
190151	1361496	<0.005	<1	3.54	9	263	<2	26	1.10	<4	5	30	17	0.84	<0.01	10	0.43	268	<1	49	376	30	0.62	<5	<5	<10	171	1277	3	24	<10	4	79
190152	1361497	<0.005	<1	4.26	12	307	<2	2	1.16	<4	7	28	17	1.21	<0.01	17	0.60	261	<1	47	401	22	0.78	<5	6	<10	166	1364	2	24	<10	5	51
190153D	1361497	<0.005	<1	4.17	9	298	<2	16	1.10	<4	6	22	17	1.24	<0.01	16	0.67	257	<1	37	408	20	0.76	<5	<5	<10	154	1424	<2	24	<10	6	50
190154	1361498	0.007	<1	4.23	23	290	<2	15	1.22	<4	25	34	14	1.92	<0.01	11	0.40	295	<1	77	360	25	1.51	<5	<5	<10	170	1197	2	22	<10	6	210
190155	1361499	<0.005	<1	4.33	7	276	<2	16	1.29	<4	7	32	12	1.50	<0.01	13	0.51	329	<1	55	382	15	0.51	<5	<5	<10	177	1393	<2	23	<10	6	44
190156	1361500	0.232	<1	<0.01	403	>5000	<2	19	0.61	<4	7	13	34	2.74	<0.01	<1	0.19	<100	2	9	<100	14	0.51	22	6	<10	115	777	3	9	46	8	<1
190157	1365001	0.020	<1	4.77	16	606	2	8	1.32	<4	18	133	40	3.21	<0.01	18	1.16	506	<1	92	534	14	2.06	<5	<5	<10	326	2066	4	81	<10	15	33
190158	1365002	0.014	<1	5.02	22	351	2	7	2.12	4	20	121	31	3.63	<0.01	21	1.46	944	<1	68	546	21	2.80	<5	<5	<10	418	1825	3	74	<10	15	84
190159	1365003	0.016	<1	6.18	29	304	2	16	1.42	4	25	132	53	4.05	<0.01	19	0.93	519	<1	79	542	22	2.82	5	<5	<10	346	1971	3	100	<10	18	35
190160	1365004	0.009	<1	5.14	12	732	<2	10	2.42	<4	14	64	19	2.54	<0.01	24	1.34	707	<1	46	414	17	1.26	<5	5	<10	340	1741	5	52	<10	12	23

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/04/2012
 Date Completed: 07/18/2012
 Job #: 201242544
 Reference: TL 12 273
 Sample #: 118

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
190161	1365005	0.012	<1	5.81	9	617	<2	18	1.79	<4	16	89	20	2.96	<0.01	25	1.35	844	<1	51	583	18	1.47	<5	<5	<10	331	2354	4	65	<10	14	53
190162	1365006	0.013	<1	3.33	13	407	<2	5	1.00	<4	9	32	8	1.80	<0.01	16	0.83	469	<1	29	516	16	0.98	5	<5	<10	224	1585	5	40	<10	7	88
190163	1365007	<0.005	<1	3.13	8	405	<2	12	1.19	<4	7	17	9	1.55	<0.01	13	0.70	381	<1	23	451	13	0.98	<5	<5	<10	208	1285	<2	28	<10	7	29
190164D	1365007	0.007	<1	2.44	8	381	<2	5	1.17	<4	7	15	9	1.59	<0.01	12	0.66	389	<1	24	450	14	0.94	<5	5	<10	202	1278	2	28	<10	6	25
190165	1365008	0.029	<1	4.89	24	464	<2	9	1.63	<4	7	17	10	1.77	<0.01	15	0.74	462	<1	25	487	19	1.40	<5	<5	<10	236	1407	2	29	<10	7	71
190166	1365009	0.008	<1	4.50	24	381	<2	13	2.08	<4	8	17	10	1.77	<0.01	14	0.82	463	<1	24	524	17	1.39	<5	5	<10	181	1275	3	30	<10	6	38
190167	1365010	<0.005	<1	4.55	6	382	<2	12	2.18	<4	17	49	26	3.31	<0.01	12	1.39	649	<1	25	598	4	0.37	<5	<5	<10	257	2608	3	111	16	19	34
190168	1365011	0.011	<1	3.53	21	339	<2	19	1.27	<4	8	20	12	1.78	<0.01	11	0.60	558	<1	30	492	23	1.19	<5	<5	<10	148	1537	5	31	<10	7	162
190169	1365012	0.014	<1	4.41	8	314	<2	6	2.56	<4	7	20	15	1.41	<0.01	8	0.73	587	<1	29	486	36	0.69	<5	<5	<10	164	1114	<2	25	<10	7	49
190170	1365013	<0.005	<1	4.43	6	347	<2	<1	2.00	<4	7	27	12	1.44	<0.01	12	0.88	624	<1	42	468	25	0.76	<5	<5	<10	141	1224	6	26	<10	7	58
190171	1365014	<0.005	<1	5.69	10	431	2	6	2.40	<4	9	21	13	1.90	<0.01	16	0.97	736	<1	31	509	30	0.85	<5	6	<10	156	1362	5	30	<10	7	63
190172	1365015	0.024	<1	3.51	39	569	<2	7	0.85	<4	10	28	6	1.97	<0.01	9	0.60	519	<1	43	512	30	1.51	<5	<5	<10	158	1785	4	29	12	7	482
190173	1365016	0.022	<1	4.85	32	504	2	11	1.07	<4	9	20	6	1.79	<0.01	14	0.49	416	<1	29	445	36	1.54	<5	<5	<10	191	1477	4	25	<10	7	241
190174	1365017	0.009	<1	4.42	29	548	2	3	1.49	<4	7	19	26	1.71	<0.01	16	1.01	1149	<1	28	495	71	1.05	<5	<5	<10	197	1481	3	28	<10	7	143
190175D	1365017	<0.005	<1	5.63	32	574	9	16	1.60	9	13	21	27	1.67	<0.01	21	0.96	1147	<1	29	479	65	1.04	<5	11	<10	220	1512	6	37	<10	17	161
190176	1365018	0.064	2	4.17	26	665	2	7	0.55	<4	7	24	16	1.72	<0.01	9	0.48	483	<1	38	486	74	1.28	<5	<5	<10	114	1584	4	29	<10	6	251
190177	1365019	0.034	<1	5.10	17	566	<2	6	1.92	<4	8	33	16	1.91	<0.01	17	1.08	1506	<1	51	486	74	0.88	<5	12	<10	146	1590	5	31	<10	7	274
190178	1365020	4.890	63	2.53	37	441	<2	1	1.21	24	14	31	62	3.36	<0.01	7	0.78	526	<1	23	550	571	0.60	56	7	230	217	1734	4	90	50	14	1895
190179	1365021	<0.005	<1	5.67	12	521	2	14	2.11	<4	9	21	22	1.88	<0.01	20	1.03	877	<1	30	486	39	0.64	5	<5	<10	155	1746	4	33	<10	8	108
190180	1365022	0.006	<1	5.65	13	522	7	22	2.83	7	15	23	15	2.01	<0.01	16	1.20	628	<1	35	542	24	0.49	<5	8	<10	192	1703	10	38	<10	14	84

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/04/2012
 Date Completed: 07/18/2012
 Job #: 201242544
 Reference: TL 12 273
 Sample #: 118

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
190181	1365023	0.005	6	4.78	22	644	2	7	0.28	<4	9	18	25	1.27	<0.01	8	0.44	204	<1	31	477	299	0.89	9	<5	<10	86	1745	8	32	<10	7	435
190182	1365024	0.602	5	3.17	21	521	<2	16	0.17	<4	9	17	23	1.18	<0.01	5	0.36	161	<1	29	464	302	0.90	5	<5	<10	72	1451	<2	26	<10	6	422
190183	1365025	0.025	<1	3.11	16	439	<2	4	0.36	<4	8	11	21	1.01	<0.01	5	0.44	323	<1	23	424	56	0.61	<5	<5	<10	81	1283	<2	24	<10	5	138
190184	1365026	0.018	<1	3.92	12	454	<2	14	1.43	<4	9	19	21	1.68	<0.01	11	0.86	871	<1	31	563	89	0.65	<5	7	<10	128	1495	4	29	<10	6	290
190185	1365027	0.289	14	3.72	26	524	<2	9	0.43	4	12	41	22	1.40	<0.01	5	0.46	354	<1	64	526	169	0.94	<5	<5	<10	99	1483	3	29	12	5	875
190186R	1365027	0.271	12	3.38	31	517	<2	2	0.35	4	12	32	22	1.29	<0.01	5	0.45	346	<1	54	501	157	0.88	<5	7	<10	91	1460	<2	28	14	6	749
190187	1365028	0.425	8	4.16	36	555	<2	12	<0.01	4	16	32	20	1.48	<0.01	5	0.30	103	<1	59	528	205	1.26	<5	<5	<10	79	1689	3	32	<10	6	712
190188	1365029	0.021	<1	6.25	20	666	2	7	2.52	<4	13	47	26	2.49	0.01	21	1.47	1304	<1	79	566	98	1.24	7	<5	<10	155	1760	3	37	<10	8	211
190189	1365030	<0.005	<1	2.67	6	364	<2	13	2.18	<4	17	51	28	3.53	<0.01	8	1.40	683	<1	29	628	3	0.29	<5	<5	<10	239	2510	4	118	18	17	41
190190	1365031	0.014	<1	5.48	14	600	3	15	2.93	4	9	26	27	2.31	<0.01	15	1.26	667	<1	38	758	76	0.97	<5	<5	<10	182	1812	4	37	<10	8	513
190191	1365032	0.298	3	2.77	49	454	2	11	0.47	4	10	31	31	2.18	<0.01	9	0.43	187	<1	42	443	334	1.73	<5	<5	<10	115	1535	3	28	12	6	779
190192	1365033	0.056	<1	4.19	23	402	2	16	2.64	<4	16	83	56	3.17	<0.01	17	1.40	670	<1	67	514	42	1.76	<5	<5	<10	121	1853	4	63	<10	11	95
190193	1365034	0.188	<1	5.30	23	475	2	12	2.26	<4	12	76	35	2.52	<0.01	20	1.23	485	<1	71	526	34	0.81	5	<5	<10	126	1930	3	49	<10	10	45
190194	1365035	0.965	1	3.55	57	374	2	13	1.06	5	15	65	70	2.72	<0.01	12	0.75	374	<1	66	604	452	1.96	5	7	<10	109	1674	3	45	13	10	780
190195	1365036	0.531	<1	2.99	57	331	2	9	1.02	5	14	56	86	2.63	<0.01	9	0.63	353	<1	57	607	491	1.97	<5	5	<10	113	1551	4	42	14	11	901
190196	1365037	0.301	<1	3.84	37	339	2	19	2.05	4	11	33	109	2.16	<0.01	20	1.18	512	<1	47	877	241	1.18	<5	<5	<10	148	1623	3	33	12	9	705
190197D	1365037	0.297	<1	4.73	36	355	2	14	2.09	4	10	34	113	2.16	<0.01	22	1.07	521	<1	52	898	237	1.16	<5	<5	<10	152	1691	6	35	13	9	697
190198	1365038	0.332	<1	4.15	40	308	2	7	1.55	4	21	112	67	3.17	<0.01	17	1.09	607	<1	81	623	86	1.39	<5	<5	<10	114	2147	6	65	10	13	232
190199	1365039	0.465	<1	4.68	23	314	2	8	1.62	<4	9	25	20	1.86	<0.01	16	0.91	455	<1	37	524	152	0.68	<5	5	<10	120	1744	4	32	<10	7	141
190200	1365040	1.947	<1	4.77	13	448	2	22	2.31	4	19	54	41	4.12	0.45	14	1.33	741	<1	30	679	16	0.34	<5	<5	<10	277	2864	4	130	21	18	46

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/04/2012
 Date Completed: 07/18/2012
 Job #: 201242544
 Reference: TL 12 273
 Sample #: 118

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
190201	1365041	0.069	<1	6.24	28	341	2	8	2.24	<4	9	17	13	2.05	<0.01	23	1.03	484	<1	23	582	36	0.78	<5	5	<10	138	2046	4	36	<10	9	230
190202	1365042	0.200	<1	6.35	19	330	2	4	2.32	<4	9	26	11	2.05	0.03	22	1.22	459	<1	42	564	37	0.62	5	7	<10	132	1921	2	34	<10	8	71
190203	1365043	0.092	<1	5.71	23	370	2	11	2.01	<4	8	38	21	1.97	0.01	20	1.05	446	<1	61	568	40	0.57	<5	<5	<10	129	1896	6	35	<10	7	121
190204	1365044	<0.005	<1	4.32	5	529	2	10	2.56	<4	7	20	17	1.92	<0.01	23	1.04	329	<1	32	534	19	0.43	<5	6	<10	253	1420	<2	30	<10	6	48
190205	1365045	0.006	<1	3.17	<2	242	<2	10	0.05	<4	5	34	13	1.41	<0.01	10	0.63	<100	<1	60	274	12	0.63	<5	8	<10	92	810	<2	12	<10	4	4
190206	1365046	<0.005	<1	2.49	10	111	<2	14	<0.01	<4	3	16	6	1.11	<0.01	24	1.24	112	<1	28	248	6	0.46	5	5	<10	89	387	8	8	<10	4	47
190207	1365047	0.008	<1	4.24	24	102	<2	8	<0.01	<4	3	21	5	1.29	<0.01	44	1.48	104	<1	30	246	7	0.80	5	<5	<10	98	388	3	9	<10	5	22
190208D	1365047	0.005	<1	4.55	21	115	<2	5	<0.01	<4	2	24	5	1.42	0.08	47	1.61	115	<1	36	272	6	0.84	<5	5	<10	104	437	2	11	<10	5	29
190209	1365048	0.025	<1	2.89	24	186	2	12	0.16	<4	4	13	3	1.45	<0.01	11	0.56	100	<1	25	243	12	1.26	<5	7	<10	93	752	3	11	<10	4	16
190210	1365049	0.015	<1	4.57	8	277	2	14	1.12	<4	4	20	11	1.10	<0.01	16	1.10	263	<1	35	269	18	0.57	<5	<5	<10	88	927	4	13	<10	5	25
190211	1365050	<0.005	<1	2.60	8	356	<2	11	1.98	<4	17	50	29	3.54	<0.01	8	1.25	660	<1	27	614	8	0.26	<5	<5	<10	242	2589	3	115	15	17	56
190212	1365051	0.297	<1	3.79	26	283	<2	8	0.47	<4	5	19	76	1.22	<0.01	7	0.64	181	<1	35	251	50	0.85	<5	<5	<10	63	943	2	14	<10	6	425
190213	1365052	0.045	<1	3.55	20	269	2	11	0.90	<4	4	22	16	1.07	<0.01	11	0.70	276	<1	43	223	34	0.61	6	<5	<10	70	872	3	11	<10	5	70
190214	1365053	1.247	<1	3.65	47	230	2	16	0.25	8	4	21	404	2.84	<0.01	10	0.41	117	<1	39	176	497	2.78	5	6	<10	52	776	<2	9	17	5	1906
190215	1365054	0.020	<1	2.95	12	231	2	12	1.08	<4	3	16	23	0.97	<0.01	12	0.94	317	<1	30	214	52	0.52	<5	5	<10	69	788	3	9	<10	5	84
190216	1365055	0.018	<1	3.08	13	262	<2	3	0.88	<4	4	23	6	0.95	<0.01	11	0.79	269	<1	36	236	23	0.43	<5	<5	<10	55	841	3	10	<10	5	23
190217	1365056	0.011	<1	3.42	17	240	2	12	0.93	<4	3	18	5	0.93	<0.01	11	0.71	268	<1	25	237	22	0.50	<5	6	<10	56	872	2	10	<10	5	23
190218	1365057	0.013	<1	3.42	10	241	2	10	1.27	<4	3	20	6	1.09	<0.01	11	0.90	368	<1	30	220	23	0.48	6	<5	<10	63	849	2	10	<10	5	23
190219D	1365057	0.010	<1	3.02	6	242	<2	11	1.31	<4	4	21	6	1.13	<0.01	10	1.04	384	<1	30	227	27	0.45	<5	<5	<10	64	825	3	9	<10	4	24
190220	1365058	0.058	<1	3.20	32	271	<2	2	0.80	<4	4	26	8	1.27	<0.01	9	0.77	288	<1	35	237	32	0.78	<5	<5	<10	54	922	<2	11	<10	5	147

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/04/2012
 Date Completed: 07/18/2012
 Job #: 201242544
 Reference: TL 12 273
 Sample #: 118

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
190221	1365059	<0.005	<1	4.39	19	283	2	15	0.94	<4	4	14	5	1.01	<0.01	13	0.88	271	<1	29	245	19	0.54	<5	5	<10	85	947	3	11	<10	6	15
190222	1365060	0.209	<1	<0.01	437	>5000	<2	21	0.69	<4	6	13	36	2.97	<0.01	<1	0.20	<100	2	10	<100	14	0.52	20	<5	<10	109	633	6	9	45	8	6
190223	1365061	0.022	<1	2.85	33	549	2	12	1.20	<4	4	13	5	1.10	<0.01	12	1.02	307	<1	27	216	17	0.38	<5	<5	<10	75	846	4	9	<10	5	12
190224	1365062	0.023	<1	4.83	18	318	<2	8	1.62	<4	4	11	7	1.15	<0.01	18	1.25	405	<1	21	233	18	0.75	<5	5	<10	91	893	2	10	<10	6	15
190225	1365063	0.123	<1	2.62	19	243	<2	8	0.52	<4	2	18	27	0.82	<0.01	8	0.67	238	<1	34	176	12	0.80	<5	5	<10	60	633	2	7	<10	5	686
190226	1365064	0.028	<1	0.63	17	168	<2	3	0.51	<4	2	13	12	0.81	<0.01	3	0.67	225	<1	33	151	19	0.49	<5	6	<10	54	552	<2	5	<10	4	220
190227	1365065	0.023	<1	0.29	4	168	<2	1	0.17	<4	3	6	44	0.92	<0.01	<1	0.49	145	<1	20	161	23	0.49	<5	<5	<10	40	512	<2	4	<10	3	306
190228	1365066	0.007	<1	0.99	2	189	<2	7	0.44	<4	1	9	20	0.69	<0.01	3	0.56	182	<1	15	193	13	0.36	<5	<5	<10	61	550	4	4	<10	4	109
190229	1365067	0.018	<1	0.84	<2	185	<2	8	0.33	<4	2	6	13	0.86	<0.01	2	0.51	158	<1	18	154	11	0.46	<5	<5	<10	57	524	5	4	<10	4	121
190230D	1365067	0.014	<1	0.25	<2	172	<2	4	0.29	<4	2	6	13	0.87	<0.01	<1	0.50	156	<1	19	146	12	0.43	<5	<5	<10	53	474	7	4	<10	4	129
190231	1365068	0.008	<1	0.23	<2	219	<2	15	0.37	<4	2	5	11	0.78	<0.01	<1	0.52	155	<1	16	152	16	0.40	<5	<5	<10	65	467	<2	4	<10	3	132
190232	1365069	0.023	<1	0.25	<2	899	<2	4	0.03	<4	3	7	10	1.03	<0.01	<1	0.38	<100	<1	20	117	13	0.54	<5	<5	<10	66	527	<2	4	<10	3	68
190233	1365070	<0.005	<1	0.52	2	283	<2	9	1.17	<4	10	28	17	2.25	<0.01	<1	0.89	429	<1	17	393	4	0.19	<5	<5	<10	170	1677	<2	72	12	12	22
190234	1365071	0.172	11	0.25	<2	278	<2	28	3.62	28	5	2	589	4.09	<0.01	4	2.37	1213	<1	12	129	1335	2.21	<5	<5	<10	132	542	9	8	64	5	10474
190235	1365072	0.044	<1	1.55	<2	669	<2	6	1.27	9	2	10	63	1.65	<0.01	8	1.81	381	<1	24	162	155	0.77	<5	6	<10	132	590	3	6	22	4	2354
190236	1365073	0.022	<1	1.71	6	915	<2	7	1.06	4	2	18	10	0.97	<0.01	5	1.23	243	<1	38	159	12	0.47	<5	<5	<10	131	595	2	7	10	4	1014
190237	1365074	0.016	<1	1.84	4	606	<2	11	1.53	<4	2	29	56	1.17	<0.01	5	1.40	400	<1	57	177	125	0.42	<5	5	<10	126	624	4	8	<10	4	472
190238	1365075	0.027	<1	1.06	3	321	<2	10	0.69	<4	2	23	26	1.15	<0.01	8	1.54	311	<1	48	154	37	0.34	<5	6	<10	79	554	<2	6	<10	3	262
190239	1365076	0.015	<1	1.22	<2	313	<2	4	0.67	<4	1	12	21	1.16	<0.01	9	1.74	319	<1	29	171	26	0.35	<5	<5	<10	79	579	6	6	<10	3	128
190240	1365077	0.173	<1	0.31	<2	181	<2	6	0.40	7	3	16	80	1.30	<0.01	2	1.14	261	<1	38	152	120	0.66	<5	<5	<10	61	475	2	5	13	3	1561

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012

Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/04/2012
 Date Completed: 07/18/2012
 Job #: 201242544
 Reference: TL 12 273
 Sample #: 118

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
190241D	1365077	0.149	<1	0.50	<2	173	<2	9	0.39	7	3	11	89	1.34	<0.01	3	1.13	265	<1	27	161	134	0.71	<5	<5	<10	60	498	<2	5	15	3	1723
190242	1365078	0.075	<1	1.10	2	230	<2	11	1.06	<4	2	30	87	1.37	<0.01	5	1.29	311	<1	61	163	39	0.55	<5	<5	<10	70	602	5	7	<10	4	472
190243	1365079	1.061	<1	0.68	8	257	<2	4	0.62	<4	3	34	306	1.19	<0.01	4	1.14	278	<1	67	163	55	0.47	<5	<5	<10	64	622	<2	7	<10	4	510
190244	1365080	4.841	41	<0.01	25	297	<2	14	0.57	16	10	19	60	2.14	<0.01	<1	0.65	337	<1	17	361	380	0.35	39	<5	153	146	1099	2	55	34	10	1277
190245	1365081	0.020	<1	0.73	15	287	<2	7	0.17	<4	3	22	10	1.01	<0.01	5	0.93	210	<1	45	186	29	0.35	<5	<5	12	65	724	3	12	<10	4	103
190246	1365082	0.006	<1	0.90	4	326	<2	9	<0.01	<4	2	14	9	0.74	<0.01	6	0.82	149	<1	31	155	9	0.29	<5	<5	<10	66	609	<2	6	<10	4	22
190247	1365083	0.011	<1	0.90	8	292	<2	14	0.14	<4	2	9	8	0.78	<0.01	8	0.87	175	<1	21	175	1	0.30	5	<5	<10	62	671	<2	7	<10	4	593
190248	1365084	0.008	<1	1.82	<2	290	<2	4	0.63	<4	2	11	3	0.87	<0.01	8	0.81	195	<1	25	167	2	0.29	<5	5	<10	86	715	2	7	<10	4	28
190249	1365085	0.020	<1	2.23	19	253	<2	7	0.52	<4	2	13	18	0.79	<0.01	11	0.77	177	<1	28	159	8	0.40	<5	<5	<10	79	666	<2	7	<10	5	173

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Wednesday, August 22, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/16/2012
 Date Completed: 08/01/2012
 Job #: 201242668
 Reference: TL 12 274
 Sample #: 138

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm	
199840	1367001	0.306	5	3.12	30	594	2	2	0.86	4	10	16	33	2.09	<0.01	4	0.72	450	8	26	583	385	1.78	<5	<5	<10	147	2183	<2	43	15	7	1150	
199841	1367002	0.141	2	2.81	43	608	2	11	0.66	<4	11	33	19	1.95	<0.01	5	0.63	397	10	39	565	247	1.57	<5	<5	<10	138	2189	<2	44	<10	7	389	
199842	1367003	0.042	1	3.41	17	578	2	<1	1.70	<4	11	26	20	2.06	<0.01	10	1.13	688	10	31	560	27	1.00	5	<5	<10	214	2187	3	47	<10	8	74	
199843	1367004	0.056	1	3.28	18	514	2	9	2.01	<4	9	24	25	1.96	<0.01	9	1.22	616	9	29	512	36	0.93	<5	<5	<10	262	1844	7	41	<10	7	147	
199844	1367005	3.101	5	3.46	36	587	2	9	0.81	13	10	27	16	2.30	<0.01	10	0.79	345	11	36	542	1371	2.09	5	<5	<10	233	2117	<2	44	46	7	4417	
199845	1367006	0.019	1	2.15	15	525	<2	6	1.05	<4	9	20	12	1.93	<0.01	13	1.14	497	10	25	521	24	0.72	<5	<5	<10	198	1981	7	42	<10	7	102	
199846	1367007	0.014	1	2.75	17	497	<2	2	1.51	<4	10	13	23	2.13	<0.01	9	1.20	759	9	24	574	16	1.12	<5	<5	<10	182	1819	3	43	<10	7	83	
199847	1367008	0.038	1	1.62	5	350	<2	<1	0.70	<4	5	14	7	0.50	<0.01	5	0.70	227	6	25	367	16	0.32	<5	<5	<10	120	1361	<2	28	<10	5	24	
199848	1367009	<0.005	1	1.80	8	357	2	13	0.77	<4	5	13	7	0.48	<0.01	4	0.68	219	6	23	367	13	0.32	<5	<5	<10	128	1334	3	27	<10	5	21	
199849	1367010	<0.005	1	1.88	<2	365	2	<1	2.19	<4	17	52	24	3.41	<0.01	2	1.42	679	13	33	606	7	0.29	<5	<5	<10	263	2665	5	116	17	17	55	
199850D	1367010																																	
																	IS																	
199851	1367011	0.021	1	2.44	16	479	2	12	0.91	<4	7	21	8	0.70	<0.01	6	0.78	297	8	29	305	58	0.68	<5	<5	<10	170	1285	6	25	<10	5	105	
199852	1367012	0.016	2	1.81	11	406	<2	11	0.79	<4	4	14	11	0.64	<0.01	3	0.70	226	5	23	342	43	0.54	<5	5	<10	141	1265	3	24	<10	4	90	
199853	1367013	0.015	1	3.12	6	495	<2	<1	1.21	<4	7	14	16	0.76	<0.01	7	0.72	201	6	23	392	12	0.61	<5	<5	<10	172	1390	4	29	<10	5	34	
199854	1367014	0.078	2	3.26	14	594	2	<1	0.68	<4	5	14	39	0.80	<0.01	8	0.75	249	7	22	408	212	0.77	<5	<5	<10	168	1576	4	28	11	5	505	
199855	1367015	0.014	1	3.85	15	594	2	<1	1.03	<4	8	13	10	0.80	<0.01	6	0.52	158	6	22	391	19	0.77	<5	<5	<10	197	1509	<2	27	<10	5	34	
199856	1367016	0.007	1	1.88	18	538	2	3	0.45	<4	11	22	12	1.06	<0.01	6	0.61	210	6	28	519	18	0.86	<5	<5	<10	108	1870	<2	34	<10	5	33	
199857	1367017	0.005	1	4.34	16	605	2	9	1.22	<4	6	22	14	1.29	<0.01	15	0.87	260	9	54	541	7	0.73	5	<5	<10	165	1954	<2	39	<10	6	36	
199858	1367018	0.008	1	3.76	11	532	2	8	1.17	<4	6	22	15	1.07	<0.01	15	0.82	333	10	22	518	20	0.93	<5	<5	<10	159	1776	4	36	<10	6	48	
199859	1367019	0.016	1	5.25	21	622	2	11	1.53	<4	6	19	11	0.93	<0.01	12	0.55	243	8	18	514	13	0.84	<5	<5	<10	212	1902	<2	38	<10	6	28	

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Wednesday, August 22, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/16/2012
 Date Completed: 08/01/2012
 Job #: 201242668
 Reference: TL 12 274
 Sample #: 138

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
199860	1367020	2.040	<1	1.16	12	432	2	14	2.68	4	25	74	45	5.24	<0.01	4	1.88	966	22	47	837	13	0.21	<5	<5	<10	257	3354	4	164	27	21	86
199861D	1367020	IS																															
199862	1367021	<0.005	<1	3.49	<2	444	2	7	1.81	<4	4	23	11	0.87	<0.01	6	0.56	228	7	24	500	6	0.58	<5	<5	<10	202	1635	<2	33	<10	6	41
199863	1367022	0.006	<1	0.47	3	377	<2	18	0.69	<4	5	13	12	0.86	<0.01	3	0.61	211	4	21	392	10	0.50	5	6	<10	115	1432	<2	28	<10	4	35
199864	1367023	<0.005	<1	1.46	6	423	<2	3	0.92	<4	4	12	7	0.84	<0.01	3	0.59	202	5	16	380	5	0.64	<5	<5	<10	151	1434	<2	28	<10	4	58
199865	1367024	<0.005	1	2.28	3	409	2	7	0.87	<4	4	13	11	1.01	<0.01	5	0.52	204	5	18	368	7	0.83	<5	<5	<10	142	1423	<2	27	<10	5	29
199866	1367025	<0.005	<1	0.73	8	316	2	<1	0.83	<4	2	11	11	0.87	<0.01	<1	0.37	168	2	16	368	7	0.70	6	<5	<10	115	1180	<2	25	<10	4	27
199867	1367026	0.006	1	1.49	5	372	<2	7	1.01	<4	2	14	7	1.08	<0.01	1	0.39	175	2	16	390	8	0.94	<5	<5	<10	117	1272	<2	27	<10	5	26
199868	1367027	<0.005	<1	1.22	5	372	<2	14	0.95	<4	3	10	7	0.84	<0.01	<1	0.46	174	2	15	329	7	0.53	<5	<5	<10	123	1327	3	24	<10	5	24
199869	1367028	0.034	1	4.73	12	495	2	13	2.16	<4	7	16	21	1.93	<0.01	12	1.11	595	7	23	499	18	1.17	6	<5	<10	175	1909	11	37	<10	8	150
199870	1367029	0.098	2	5.21	26	563	2	9	1.69	<4	10	16	36	1.99	<0.01	13	1.06	564	9	24	522	213	1.22	5	<5	<10	96	2082	<2	38	<10	8	267
199871	1367030	0.006	1	3.55	<2	426	2	3	2.48	<4	18	56	25	3.61	<0.01	6	1.53	732	15	34	644	8	0.36	6	<5	<10	302	3037	9	123	19	18	60
199872D	1367030	IS																															
199873	1367031	0.010	1	4.38	9	483	2	8	2.22	<4	8	17	10	1.85	<0.01	11	1.28	676	10	24	501	28	0.79	<5	<5	<10	103	1839	3	36	<10	7	69
199874	1367032	0.462	14	4.54	40	527	3	10	1.06	12	9	23	757	2.44	<0.01	11	0.92	432	12	34	483	3629	2.58	12	6	<10	87	1931	<2	37	47	7	4432
199875	1367033	0.036	2	4.14	21	508	2	14	1.93	<4	8	19	60	1.88	<0.01	10	1.24	710	10	28	481	186	1.07	<5	<5	<10	102	1924	8	38	<10	7	290
199876	1367034	0.021	1	2.82	20	452	2	<1	1.29	<4	7	16	15	1.66	<0.01	6	0.94	698	8	22	482	26	1.11	<5	<5	<10	165	1698	<2	34	<10	6	67
199877	1367035	0.030	<1	2.22	27	475	2	4	0.87	<4	6	18	7	1.37	<0.01	6	0.86	652	7	25	428	33	1.11	<5	<5	<10	149	1664	4	31	<10	5	65
199878	1367036	0.029	<1	1.19	38	433	<2	5	0.69	<4	7	13	7	1.42	<0.01	3	0.84	634	6	23	439	29	1.15	7	<5	<10	131	1580	6	29	<10	5	48
199879	1367037	2.311	3	2.13	37	426	2	12	0.61	<4	7	15	31	1.60	<0.01	3	0.68	477	4	23	519	258	1.56	<5	<5	<10	142	1766	<2	32	<10	6	261

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Wednesday, August 22, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/16/2012
 Date Completed: 08/01/2012
 Job #: 201242668
 Reference: TL 12 274
 Sample #: 138

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
199880	1367038	0.086	1	1.84	37	465	2	17	0.86	<4	7	19	25	1.62	<0.01	3	0.84	691	7	26	460	62	1.43	<5	<5	<10	157	1567	2	32	<10	5	82
199881	1367039	0.231	1	3.77	24	547	2	23	0.94	<4	6	23	25	1.29	<0.01	10	0.91	664	9	25	391	41	1.05	<5	<5	<10	185	1624	<2	33	<10	6	58
199882	1367040	0.256	1	<0.01	481	>5000	<2	5	0.70	<4	8	19	35	3.23	<0.01	<1	0.19	<100	24	15	<100	18	0.54	25	<5	<10	124	819	4	17	59	8	22
199883D	1367040																IS																
199884	1367041	0.084	1	3.01	31	667	2	5	0.52	<4	6	21	25	1.27	<0.01	8	0.81	539	7	23	404	81	1.04	5	<5	<10	162	1572	<2	33	<10	6	84
199885	1367042	0.318	2	2.75	16	874	2	<1	1.66	<4	10	51	105	1.81	<0.01	<1	1.04	481	13	48	971	274	1.34	<5	<5	<10	321	1834	<2	47	<10	9	554
199886	1367043	0.079	4	2.57	13	607	3	<1	1.83	<4	15	47	46	2.30	<0.01	9	1.57	696	14	64	1238	247	1.18	<5	<5	<10	512	2110	<2	47	<10	11	361
199887	1367044	0.099	1	3.39	15	565	2	14	0.92	<4	8	17	20	1.41	<0.01	8	0.96	847	9	25	621	63	1.28	<5	<5	<10	198	1823	<2	36	<10	7	73
199888	1367045	0.272	2	2.96	33	431	<2	3	0.68	<4	7	19	24	1.23	<0.01	6	0.74	625	6	22	440	130	1.24	<5	<5	<10	149	1655	<2	33	<10	6	166
199889	1367046	0.373	3	3.02	38	404	2	<1	0.87	<4	7	18	63	1.72	<0.01	6	0.92	825	8	25	429	165	1.74	<5	<5	<10	157	1550	3	33	<10	6	627
199890	1367047	0.292	5	3.82	50	504	2	7	0.93	<4	12	38	41	1.98	<0.01	6	0.94	731	11	33	567	560	1.98	<5	<5	<10	186	2076	<2	45	<10	8	581
199891	1367048	0.545	7	4.29	27	467	2	10	0.68	<4	9	30	48	1.26	<0.01	4	0.76	539	9	25	492	537	1.28	7	9	<10	199	1919	<2	35	11	7	661
199892	1367049	0.049	2	5.04	24	480	2	<1	0.94	<4	7	21	8	1.60	<0.01	9	0.92	720	9	27	449	47	1.47	<5	<5	<10	208	1782	<2	32	<10	6	144
199893	1367050	<0.005	<1	2.09	<2	384	2	10	2.32	<4	18	56	25	3.63	<0.01	3	1.51	736	13	35	640	8	0.30	<5	<5	<10	273	2891	5	122	21	17	59
199894D	1367050																IS																
199895	1367051	0.026	1	4.49	12	405	2	10	1.58	<4	6	20	11	1.21	<0.01	8	1.01	662	13	31	447	20	0.75	<5	<5	<10	229	1728	2	30	<10	6	66
199896	1367052	0.006	1	4.55	7	453	2	5	1.45	<4	6	20	6	1.26	<0.01	10	0.84	516	8	24	460	15	0.74	7	<5	<10	189	1754	4	32	<10	6	54
199897	1367053	0.006	2	3.56	2	437	3	4	2.21	<4	6	21	10	1.71	<0.01	8	1.36	1171	10	24	423	31	0.62	<5	<5	<10	210	1481	2	33	<10	6	109
199898	1367054	0.008	1	3.66	7	248	2	4	1.96	<4	6	17	4	1.51	<0.01	8	1.15	798	6	17	376	16	0.61	<5	<5	<10	212	1437	3	27	<10	5	36
199899	1367055	0.005	2	4.36	9	284	2	<1	2.37	<4	6	28	40	1.65	<0.01	11	0.97	579	10	127	425	14	0.87	6	<5	<10	214	1677	12	32	<10	8	231

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Wednesday, August 22, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/16/2012
 Date Completed: 08/01/2012
 Job #: 201242668
 Reference: TL 12 274
 Sample #: 138

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
199900	1367056	0.007	1	3.31	19	257	2	<1	1.77	<4	5	24	39	1.44	<0.01	8	0.84	486	7	153	391	5	0.76	<5	<5	<10	191	1528	2	31	<10	7	46
199901	1367057	<0.005	1	3.56	8	318	<2	15	1.55	<4	4	22	47	1.23	<0.01	7	0.59	336	7	168	416	18	0.77	<5	6	<10	191	1516	8	31	<10	6	42
199902	1367058	0.009	1	3.61	10	381	2	4	1.08	<4	5	24	33	0.90	<0.01	10	0.54	252	9	131	337	23	0.61	8	<5	<10	225	1415	2	29	<10	5	96
199903	1367059	0.007	1	3.23	8	482	2	<1	1.05	<4	8	22	45	1.46	<0.01	14	0.81	424	8	162	400	27	1.06	<5	<5	<10	305	1574	10	30	<10	6	74
199904	1367060	3.988	74	<0.01	48	417	2	4	1.14	23	17	36	78	3.59	<0.01	<1	0.94	548	15	118	584	646	0.58	43	<5	279	214	1840	<2	100	57	14	2119
199905R	1367060																IS																
199906	1367061	<0.005	2	3.24	19	200	2	11	2.56	<4	20	21	50	3.84	<0.01	6	0.52	448	17	177	515	31	4.38	<5	<5	<10	235	1573	<2	35	28	7	189
199907	1367062	<0.005	1	2.77	25	292	2	<1	1.36	<4	29	19	31	2.83	<0.01	6	0.45	274	12	165	389	20	3.06	<5	<5	<10	204	1395	3	27	<10	5	302
199908	1367063	<0.005	1	2.52	<2	266	<2	<1	1.50	<4	6	17	50	1.43	<0.01	5	0.52	374	6	164	376	14	0.56	<5	<5	<10	202	1464	<2	27	<10	6	43
199909	1367064	0.039	5	2.56	57	391	2	8	2.46	<4	17	87	93	2.80	<0.01	2	0.85	712	15	218	558	30	1.50	<5	<5	<10	273	1710	6	48	<10	14	63
199910	1367065	0.394	9	2.47	20	409	2	<1	0.43	<4	8	24	91	1.87	<0.01	4	0.52	316	8	184	536	49	1.29	<5	<5	<10	164	1785	<2	34	12	7	566
199911	1367066	0.056	2	3.83	22	427	<2	2	1.43	<4	9	17	90	1.68	<0.01	9	0.71	408	8	234	604	24	0.85	5	<5	<10	175	2058	10	39	<10	7	263
199912	1367067	<0.005	1	3.37	9	361	2	7	2.65	<4	9	16	58	2.00	<0.01	10	1.06	615	9	222	621	12	0.52	<5	<5	<10	212	2077	2	39	<10	7	62
199913	1367068	<0.005	2	4.71	12	529	2	<1	2.48	<4	9	16	49	1.85	<0.01	11	1.17	733	10	181	627	28	0.70	<5	<5	<10	236	2105	9	41	<10	7	87
199914	1367069	0.135	33	4.61	36	580	2	<1	1.15	5	13	24	101	2.28	<0.01	9	0.98	1117	11	317	574	603	2.14	12	6	<10	206	1931	3	42	18	7	1474
199915	1367070	<0.005	1	2.58	<2	394	2	14	2.40	<4	17	58	51	3.67	<0.01	4	1.53	743	16	144	661	9	0.32	<5	5	<10	282	2981	5	125	22	18	70
199916D	1367070																IS																
199917	1367071	0.175	8	1.84	35	596	2	9	<0.01	<4	9	19	92	1.53	<0.01	<1	0.26	<100	6	139	478	219	1.69	<5	<5	<10	104	1519	<2	33	11	6	818
199918	1367072	0.183	7	2.89	35	702	2	8	0.39	<4	7	27	70	1.65	<0.01	<1	0.56	589	6	170	545	282	1.53	<5	<5	<10	170	1697	<2	37	10	6	603
199919	1367073	0.124	8	4.15	36	865	3	10	0.26	<4	9	23	64	1.73	<0.01	<1	0.50	327	9	175	597	207	1.65	<5	<5	<10	155	1943	2	41	11	7	325

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Wednesday, August 22, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/16/2012
 Date Completed: 08/01/2012
 Job #: 201242668
 Reference: TL 12 274
 Sample #: 138

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
199920	1367074	0.030	2	3.42	32	573	2	3	1.12	<4	11	31	56	2.05	<0.01	3	0.84	807	10	188	564	55	1.53	<5	<5	<10	166	1875	<2	39	10	7	141
199921	1367075	0.044	3	3.41	22	524	3	17	1.52	<4	9	22	47	1.84	<0.01	5	1.00	770	7	158	564	53	1.15	<5	<5	<10	155	1797	6	37	11	6	163
199922	1367076	0.046	3	3.83	19	531	3	16	1.59	<4	9	30	54	1.92	<0.01	7	1.02	792	8	161	558	56	1.23	<5	<5	<10	159	1803	5	38	<10	7	136
199923	1367077	1.257	11	2.73	22	505	2	7	<0.01	<4	9	22	59	1.16	0.11	<1	0.32	<100	7	79	409	204	1.12	6	<5	<10	87	1587	<2	34	14	6	851
199924	1367078	1.268	13	2.91	27	520	2	11	0.11	<4	7	26	90	1.44	<0.01	<1	0.36	164	7	166	465	384	1.46	5	<5	<10	102	1529	2	34	16	7	1062
199925	1367079	0.093	2	3.07	22	620	2	3	0.66	<4	8	28	71	1.52	0.11	3	0.68	456	8	203	520	60	1.04	<5	<5	<10	108	1753	<2	36	<10	6	126
199926	1367080	6.072	1	2.43	6	404	2	3	2.26	<4	18	58	79	4.07	<0.01	5	1.54	764	18	218	664	8	0.30	7	<5	<10	268	2916	2	128	23	18	68
199927D	1367080																IS																
199928	1367081	0.025	3	2.59	9	621	2	9	0.49	<4	10	17	59	1.65	<0.01	2	0.59	442	19	190	485	48	1.07	<5	<5	<10	115	1753	<2	36	10	6	178
199929	1367082	0.021	2	<0.01	<2	524	2	<1	<0.01	<4	8	37	65	1.48	<0.01	<1	0.27	123	6	167	345	27	1.00	<5	<5	<10	96	1273	<2	25	<10	5	55
199930	1367083	0.007	2	2.66	2	492	4	7	3.11	<4	6	28	57	1.67	<0.01	4	1.08	737	8	171	620	80	0.62	6	7	<10	181	1292	4	27	<10	6	109
199931	1367084	0.010	2	4.57	<2	739	4	14	2.78	<4	8	19	67	1.86	<0.01	10	0.88	521	6	184	663	52	0.97	<5	<5	<10	212	1915	3	34	<10	8	68
199932	1367085	0.005	1	5.26	<2	849	2	19	2.35	<4	9	24	67	1.86	<0.01	16	1.27	481	10	197	574	28	0.70	<5	<5	<10	214	1983	8	41	<10	8	39
199933	1367086	<0.005	2	4.79	2	869	2	6	2.94	<4	9	23	57	1.98	<0.01	19	1.49	575	4	168	558	71	0.40	<5	<5	<10	203	1935	<2	40	<10	7	70
199934	1367087	<0.005	1	4.60	4	707	2	19	2.10	<4	7	22	55	1.84	<0.01	16	1.28	474	9	174	540	31	0.76	6	<5	<10	197	1983	<2	39	<10	7	63
199935	1367088	0.012	2	4.46	19	584	2	<1	0.19	<4	8	19	48	1.55	<0.01	2	0.43	107	7	147	548	23	1.56	<5	<5	<10	115	2060	<2	40	<10	7	164
199936	1367089	0.010	1	5.13	3	599	2	<1	2.35	<4	13	19	28	1.80	<0.01	16	1.38	508	10	105	573	32	1.08	<5	<5	<10	184	1976	5	40	<10	8	54
199937	1367090	<0.005	<1	2.00	7	350	2	9	2.30	<4	18	56	53	3.61	<0.01	4	1.50	729	14	152	648	4	0.31	<5	<5	<10	258	2970	2	120	18	18	55
199938D	1367090																IS																
199939	1367091	0.234	10	4.09	20	510	2	<1	1.04	<4	9	21	344	1.87	<0.01	8	0.75	242	8	155	549	30	1.15	<5	<5	<10	128	2159	6	42	<10	7	79

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Wednesday, August 22, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/16/2012
 Date Completed: 08/01/2012
 Job #: 201242668
 Reference: TL 12 274
 Sample #: 138

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
199940	1367092	0.034	2	5.02	26	461	3	9	2.28	<4	14	41	73	2.55	<0.01	13	1.28	505	10	167	596	53	1.51	<5	<5	<10	148	2399	3	54	<10	9	138
199941	1367093	0.022	2	4.06	20	434	3	14	2.29	<4	13	59	46	2.33	<0.01	10	1.21	450	10	107	503	34	0.97	5	<5	<10	107	1935	2	51	<10	10	92
199942	1367094	0.395	2	0.24	41	277	2	<1	<0.01	<4	7	21	56	1.38	<0.01	<1	0.44	160	4	144	455	70	1.22	<5	<5	<10	53	1244	<2	29	<10	5	167
199943	1367095	0.298	2	0.18	57	259	2	<1	<0.01	<4	7	20	66	1.46	<0.01	<1	0.23	<100	3	142	469	110	1.49	<5	<5	<10	38	1215	<2	29	<10	5	163
199944	1367096	0.395	5	2.36	71	316	2	4	<0.01	<4	9	23	104	1.68	<0.01	<1	0.31	<100	6	186	523	213	1.78	<5	<5	<10	52	1453	<2	35	<10	6	241
199945	1367097	0.059	1	3.37	8	350	2	<1	1.43	<4	9	23	62	1.85	<0.01	5	1.03	523	6	161	557	47	0.94	<5	<5	<10	96	1583	<2	37	<10	7	126
199946	1367098	0.504	3	3.88	35	291	2	8	1.84	5	8	24	117	2.01	<0.01	7	1.13	578	10	140	546	182	1.34	<5	<5	<10	99	1648	12	35	20	7	1078
199947	1367099	0.160	1	4.82	28	314	2	3	1.41	<4	9	21	94	1.67	<0.01	12	0.99	455	9	205	574	52	1.04	5	<5	<10	94	1961	4	38	11	8	170
199948	1367100	0.249	1	<0.01	469	4382	2	<1	0.73	<4	7	19	67	3.10	<0.01	<1	0.22	<100	22	130	<100	21	0.52	22	<5	<10	140	970	5	17	52	8	25
199949D	1367100																IS																
199950	1367101	0.130	2	3.36	31	287	2	9	1.36	<4	11	29	82	1.84	<0.01	7	0.97	469	7	167	530	62	1.08	8	<5	<10	94	1890	<2	41	<10	8	77
199951	1367102	0.020	2	4.07	5	308	2	2	1.94	<4	15	84	65	2.51	<0.01	13	1.25	585	13	163	557	39	0.73	<5	<5	<10	124	2294	5	60	<10	11	83
199952	1367103	0.037	1	4.46	15	371	2	3	1.16	<4	8	22	57	1.54	<0.01	12	0.88	349	7	112	524	39	0.76	<5	<5	<10	103	2056	10	40	13	7	272
199953	1367104	0.087	1	4.41	24	345	2	9	1.54	<4	9	23	71	1.86	<0.01	11	1.00	418	8	135	567	24	1.06	<5	<5	<10	113	2044	<2	39	<10	7	85
199954	1367105	0.045	<1	3.39	8	335	2	8	1.72	<4	8	18	54	1.84	<0.01	9	0.99	389	8	121	521	16	0.74	<5	9	<10	117	1926	<2	37	<10	6	76
199955	1367106	0.362	3	2.97	26	358	2	12	0.67	<4	7	20	147	1.59	<0.01	6	0.63	261	8	149	451	294	1.29	<5	<5	<10	100	1738	<2	34	11	6	464
199956	1367107	0.219	2	5.33	11	497	2	13	1.95	<4	11	21	124	2.10	<0.01	16	1.01	433	9	156	582	95	1.09	<5	<5	<10	156	2204	2	42	13	8	239
199957	1367108	0.015	1	4.27	6	429	2	6	2.37	<4	10	24	55	1.94	<0.01	11	1.01	443	9	165	542	24	0.56	<5	<5	<10	184	2021	<2	39	<10	7	72
199958	1367109	<0.005	1	4.39	2	290	2	16	1.47	<4	6	19	54	1.36	<0.01	9	1.43	370	13	185	267	19	0.51	<5	<5	<10	141	1061	3	20	<10	5	49
199959	1367110	<0.005	1	2.16	3	364	2	5	2.33	<4	18	57	53	3.65	<0.01	4	1.52	733	15	145	645	9	0.28	<5	<5	<10	265	2968	<2	122	18	18	56

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Wednesday, August 22, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/16/2012
 Date Completed: 08/01/2012
 Job #: 201242668
 Reference: TL 12 274
 Sample #: 138

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
199960D	1367110	IS																															
199961	1367111	0.041	1	3.06	<2	242	2	<1	0.02	<4	3	22	44	1.53	<0.01	<1	0.39	<100	7	142	262	30	1.06	<5	<5	<10	109	988	<2	19	<10	5	20
199962	1367112	0.016	1	3.75	5	215	2	<1	1.11	<4	3	26	30	1.34	<0.01	10	1.29	292	9	104	282	22	0.55	7	<5	<10	131	1011	8	18	<10	5	80
199963	1367113	0.053	1	4.38	14	315	2	2	1.40	<4	5	22	49	1.31	<0.01	10	1.11	350	10	154	259	32	0.76	<5	<5	<10	102	1051	<2	18	<10	6	56
199964	1367114	0.163	1	4.74	30	341	3	4	0.68	<4	5	17	70	1.27	<0.01	12	0.76	222	12	155	246	52	1.31	<5	<5	<10	93	1084	<2	18	<10	7	194
199965	1367115	0.288	1	3.52	27	313	3	21	0.56	5	3	23	130	1.34	<0.01	8	0.76	213	14	195	217	91	1.43	<5	<5	<10	85	955	<2	17	12	6	1145
199966	1367116	0.532	1	3.04	32	294	2	<1	0.50	5	3	23	128	1.29	<0.01	6	0.69	185	14	167	219	84	1.42	<5	<5	<10	89	906	<2	16	18	5	1157
199967	1367117	0.878	2	3.33	39	305	2	<1	0.96	17	3	19	120	1.39	<0.01	7	0.81	297	9	143	228	213	1.56	7	<5	<10	92	965	<2	17	49	6	4390
199968	1367118	0.051	1	2.89	30	351	2	2	0.86	<4	2	16	28	1.15	<0.01	12	0.85	251	6	93	264	38	1.04	<5	<5	<10	88	984	<2	17	<10	5	99
199969	1367119	0.042	1	3.94	26	349	3	13	1.60	<4	5	18	44	1.20	<0.01	19	1.23	431	9	147	251	33	0.87	<5	<5	<10	100	1046	<2	18	<10	6	55
199970	1367120	5.043	83	2.43	40	547	2	14	1.53	26	19	42	108	3.92	<0.01	4	1.08	619	20	199	669	728	0.70	54	<5	319	282	2187	<2	111	66	16	2363
199971R	1367120	IS																															
199972	1367121	0.040	1	4.66	18	360	2	16	1.81	<4	3	21	31	1.07	<0.01	20	1.39	471	13	115	283	54	0.68	<5	<5	<10	131	1059	2	17	<10	7	113
199973	1367122	0.132	2	3.08	19	284	2	<1	1.09	<4	4	20	75	1.11	<0.01	12	1.08	353	8	136	243	170	0.88	<5	<5	<10	100	958	<2	16	<10	6	701
199974	1367123	0.134	1	2.76	42	296	2	3	0.97	<4	3	17	80	1.53	<0.01	9	0.92	329	8	148	254	41	1.49	5	<5	<10	91	935	2	15	11	6	837
199975	1367124	0.033	1	2.78	28	264	2	<1	0.84	<4	4	17	47	0.98	<0.01	7	0.88	285	8	133	247	56	0.84	<5	<5	<10	92	931	<2	16	<10	6	266
199976	1367125	0.038	<1	3.30	26	293	2	2	0.79	<4	4	20	51	1.12	<0.01	8	0.90	282	8	129	249	29	1.02	<5	<5	<10	88	1035	12	17	<10	6	78
199977	1367126	0.072	<1	3.54	32	361	2	11	0.60	<4	4	16	43	1.22	<0.01	7	0.86	260	9	129	258	27	1.18	<5	<5	<10	80	1098	16	18	<10	6	391
199978	1367127	0.090	1	2.70	42	305	2	<1	0.65	<4	4	15	56	1.87	<0.01	6	1.06	284	9	136	268	38	1.68	<5	<5	<10	80	1002	<2	17	<10	5	146
199979	1367128	0.006	<1	3.44	6	316	3	<1	1.04	<4	3	15	38	1.04	<0.01	8	1.36	355	11	135	259	24	0.54	<5	<5	<10	94	1013	<2	17	<10	6	75

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Wednesday, August 22, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/16/2012
 Date Completed: 08/01/2012
 Job #: 201242668
 Reference: TL 12 274
 Sample #: 138

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
199980	1367129	0.007	1	3.87	<2	330	3	16	1.04	<4	4	16	43	1.19	<0.01	11	1.52	392	13	139	279	19	0.47	<5	<5	<10	106	1068	<2	18	<10	6	89
199981	1367130	<0.005	1	1.50	2	365	<2	9	2.22	<4	17	54	55	3.55	<0.01	2	1.47	716	13	144	634	1	0.26	<5	<5	<10	263	2817	4	120	22	17	60
199982D	1367130	IS																															
199983	1367131	<0.005	<1	1.87	<2	325	2	28	0.40	<4	5	13	31	1.18	<0.01	2	1.15	284	10	115	281	25	0.61	<5	<5	<10	93	979	2	16	<10	5	54
199984	1367132	0.010	1	0.90	<2	214	2	20	5.25	6	3	9	130	3.32	<0.01	11	5.79	2385	<1	88	198	34	1.25	<5	<5	<10	120	693	30	15	214	8	1496
199985	1367133	0.025	6	1.29	<2	177	2	30	3.80	29	3	8	140	3.16	<0.01	19	5.72	2128	24	164	291	368	1.34	6	<5	<10	121	758	15	15	93	6	183
199986	1367134	0.082	2	1.99	10	328	2	7	2.29	25	2	12	190	3.31	<0.01	5	2.70	1064	10	183	207	119	2.56	6	<5	<10	151	861	7	17	66	5	264
199987	1367135	0.020	2	2.82	4	343	4	<1	6.68	5	3	10	421	3.78	<0.01	2	3.68	1500	14	212	231	46	1.75	5	<5	12	279	874	9	18	21	7	757
199988	1367136	0.009	2	3.35	<2	445	4	12	6.21	5	4	13	439	4.13	<0.01	4	3.55	1400	8	161	218	58	2.06	5	<5	<10	284	928	16	19	18	8	906
199989	1367137	0.016	2	2.45	<2	259	2	14	3.15	<4	3	10	203	2.15	<0.01	9	3.19	1046	17	133	310	286	1.08	<5	<5	<10	131	894	6	17	10	7	301
199990	1367138	0.014	<1	2.18	9	340	2	12	0.99	<4	3	13	59	1.50	<0.01	12	2.66	483	14	113	237	34	0.66	<5	<5	<10	103	877	4	16	11	5	864

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Wednesday, August 1, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/16/2012
 Date Completed:
 Job #: 201242668
 Reference: TL 12 274
 Sample #: 138

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
199840	1367001	306	0.009	0.306
199841	1367002	141	0.004	0.141
199842	1367003	42	0.001	0.042
199843	1367004	56	0.002	0.056
199844	1367005	3101	0.090	3.101
199845	1367006	19	<0.001	0.019
199846	1367007	14	<0.001	0.014
199847	1367008	38	0.001	0.038
199848	1367009	<5	<0.001	<0.005
199849	1367010	<5	<0.001	<0.005
199850 Dup	1367010	Insufficient Sample		
199851	1367011	21	<0.001	0.021
199852	1367012	16	<0.001	0.016
199853	1367013	15	<0.001	0.015
199854	1367014	78	0.002	0.078
199855	1367015	14	<0.001	0.014
199856	1367016	7	<0.001	0.007
199857	1367017	5	<0.001	0.005
199858	1367018	8	<0.001	0.008
199859	1367019	16	<0.001	0.016
199860	1367020	2040	0.060	2.040
199861 Dup	1367020	Insufficient Sample		
199862	1367021	<5	<0.001	<0.005
199863	1367022	6	<0.001	0.006
199864	1367023	<5	<0.001	<0.005
199865	1367024	<5	<0.001	<0.005
199866	1367025	<5	<0.001	<0.005
199867	1367026	6	<0.001	0.006
199868	1367027	<5	<0.001	<0.005
199869	1367028	34	<0.001	0.034

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, August 1, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/16/2012
 Date Completed:
 Job #: 201242668
 Reference: TL 12 274
 Sample #: 138

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
199870	1367029	98	0.003	0.098
199871	1367030	6	<0.001	0.006
199872 Dup	1367030	Insufficient Sample		
199873	1367031	10	<0.001	0.010
199874	1367032	462	0.013	0.462
199875	1367033	36	0.001	0.036
199876	1367034	21	<0.001	0.021
199877	1367035	30	<0.001	0.030
199878	1367036	29	<0.001	0.029
199879	1367037	2311	0.067	2.311
199880	1367038	86	0.003	0.086
199881	1367039	231	0.007	0.231
199882	1367040	256	0.007	0.256
199883 Dup	1367040	Insufficient Sample		
199884	1367041	84	0.002	0.084
199885	1367042	318	0.009	0.318
199886	1367043	79	0.002	0.079
199887	1367044	99	0.003	0.099
199888	1367045	272	0.008	0.272
199889	1367046	373	0.011	0.373
199890	1367047	292	0.009	0.292
199891	1367048	545	0.016	0.545
199892	1367049	49	0.001	0.049
199893	1367050	<5	<0.001	<0.005
199894 Dup	1367050	Insufficient Sample		
199895	1367051	26	<0.001	0.026
199896	1367052	6	<0.001	0.006
199897	1367053	6	<0.001	0.006
199898	1367054	8	<0.001	0.008
199899	1367055	5	<0.001	0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, August 1, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/16/2012
 Date Completed:
 Job #: 201242668
 Reference: TL 12 274
 Sample #: 138

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
199900	1367056	7	<0.001	0.007
199901	1367057	<5	<0.001	<0.005
199902	1367058	9	<0.001	0.009
199903	1367059	7	<0.001	0.007
199904	1367060	3988	0.116	3.988
199905 Rep	1367060	Insufficient Sample		
199906	1367061	<5	<0.001	<0.005
199907	1367062	<5	<0.001	<0.005
199908	1367063	<5	<0.001	<0.005
199909	1367064	39	0.001	0.039
199910	1367065	394	0.011	0.394
199911	1367066	56	0.002	0.056
199912	1367067	<5	<0.001	<0.005
199913	1367068	<5	<0.001	<0.005
199914	1367069	135	0.004	0.135
199915	1367070	<5	<0.001	<0.005
199916 Dup	1367070	Insufficient Sample		
199917	1367071	175	0.005	0.175
199918	1367072	183	0.005	0.183
199919	1367073	124	0.004	0.124
199920	1367074	30	<0.001	0.030
199921	1367075	44	0.001	0.044
199922	1367076	46	0.001	0.046
199923	1367077	1257	0.037	1.257
199924	1367078	1268	0.037	1.268
199925	1367079	93	0.003	0.093
199926	1367080	6072	0.177	6.072
199927 Dup	1367080	Insufficient Sample		
199928	1367081	25	<0.001	0.025
199929	1367082	21	<0.001	0.021

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, August 1, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/16/2012
 Date Completed:
 Job #: 201242668
 Reference: TL 12 274
 Sample #: 138

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
199930	1367083	7	<0.001	0.007
199931	1367084	10	<0.001	0.010
199932	1367085	5	<0.001	0.005
199933	1367086	<5	<0.001	<0.005
199934	1367087	<5	<0.001	<0.005
199935	1367088	12	<0.001	0.012
199936	1367089	10	<0.001	0.010
199937	1367090	<5	<0.001	<0.005
199938 Dup	1367090	Insufficient Sample		
199939	1367091	234	0.007	0.234
199940	1367092	34	<0.001	0.034
199941	1367093	22	<0.001	0.022
199942	1367094	395	0.012	0.395
199943	1367095	298	0.009	0.298
199944	1367096	395	0.012	0.395
199945	1367097	59	0.002	0.059
199946	1367098	504	0.015	0.504
199947	1367099	160	0.005	0.160
199948	1367100	249	0.007	0.249
199949 Dup	1367100	Insufficient Sample		
199950	1367101	130	0.004	0.130
199951	1367102	20	<0.001	0.020
199952	1367103	37	0.001	0.037
199953	1367104	87	0.003	0.087
199954	1367105	45	0.001	0.045
199955	1367106	362	0.011	0.362
199956	1367107	219	0.006	0.219
199957	1367108	15	<0.001	0.015
199958	1367109	<5	<0.001	<0.005
199959	1367110	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, August 1, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/16/2012
 Date Completed:
 Job #: 201242668
 Reference: TL 12 274
 Sample #: 138

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
199960 Dup	1367110	Insufficient Sample		
199961	1367111	41	0.001	0.041
199962	1367112	16	<0.001	0.016
199963	1367113	53	0.002	0.053
199964	1367114	163	0.005	0.163
199965	1367115	288	0.008	0.288
199966	1367116	532	0.016	0.532
199967	1367117	878	0.026	0.878
199968	1367118	51	0.001	0.051
199969	1367119	42	0.001	0.042
199970	1367120	5043	0.147	5.043
199971 Rep	1367120	Insufficient Sample		
199972	1367121	40	0.001	0.040
199973	1367122	132	0.004	0.132
199974	1367123	134	0.004	0.134
199975	1367124	33	<0.001	0.033
199976	1367125	38	0.001	0.038
199977	1367126	72	0.002	0.072
199978	1367127	90	0.003	0.090
199979	1367128	6	<0.001	0.006
199980	1367129	7	<0.001	0.007
199981	1367130	<5	<0.001	<0.005
199982 Dup	1367130	Insufficient Sample		
199983	1367131	<5	<0.001	<0.005
199984	1367132	10	<0.001	0.010
199985	1367133	25	<0.001	0.025
199986	1367134	82	0.002	0.082
199987	1367135	20	<0.001	0.020
199988	1367136	9	<0.001	0.009
199989	1367137	16	<0.001	0.016

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, August 1, 2012


Preliminary Analysis

Treasury Metals Inc
Exchange Tower 130 King St Suite 3680
Toronto, On, CAN
M5X 1B1
Ph#: (416) 599-4133
Fax#: (416) 599-4959
Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/16/2012
Date Completed:
Job #: 201242668
Reference: TL 12 274
Sample #: 138

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
199990	1367138	14	<0.001	0.014

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


Certified By: Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
The results generated by this procedure are not accredited at this time and therefore are informational only.

Thursday, August 9, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/10/2012
 Date Completed: 07/27/2012
 Job #: 201242628
 Reference: TL 12 275
 Sample #: 100

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
196313	1365086	0.074	2	4.45	31	583	<2	1	1.66	4	13	26	16	2.74	<0.01	20	1.10	649	<1	42	677	31	1.88	<5	<5	<10	262	2691	3	56	<10	8	599
196314	1365087	0.060	4	5.03	8	498	<2	<1	2.11	<4	12	22	13	2.58	<0.01	20	1.04	630	<1	40	662	17	1.13	<5	<5	<10	298	3221	6	55	<10	8	100
196315	1365088	0.026	2	4.80	9	474	<2	2	2.10	<4	13	17	13	2.47	<0.01	20	1.01	529	<1	35	663	12	0.67	<5	<5	<10	349	3064	5	53	<10	9	62
196316	1365089	0.223	3	5.32	21	535	<2	2	1.33	4	12	26	96	2.39	<0.01	19	0.88	710	<1	45	592	122	1.75	<5	<5	<10	225	2692	3	48	16	8	676
196317	1365090	<0.005	<1	5.18	2	421	<2	5	2.29	<4	16	50	32	3.45	<0.01	11	1.36	693	<1	35	637	18	0.40	<5	<5	<10	300	2995	6	111	15	19	98
196318	1365091	0.023	1	5.90	7	472	<2	1	2.02	<4	11	35	33	2.23	<0.01	17	1.09	753	<1	45	516	34	0.85	<5	<5	<10	226	2549	3	52	<10	10	59
196319	1365092	0.080	<1	5.62	17	560	<2	5	1.62	<4	10	33	11	2.37	<0.01	17	0.98	750	<1	55	575	45	1.58	<5	<5	<10	225	2413	<2	50	<10	9	309
196320	1365093	0.032	1	5.43	19	623	<2	6	2.41	<4	10	33	7	2.30	<0.01	12	1.23	862	<1	51	601	49	1.33	<5	<5	<10	238	2437	4	48	<10	8	108
196321	1365094	0.202	6	3.65	10	509	<2	<1	1.60	6	9	34	20	1.89	<0.01	7	0.97	762	<1	56	505	411	1.43	<5	<5	<10	176	1818	3	38	12	7	1228
196322	1365095	0.085	2	4.33	17	482	<2	<1	1.70	<4	10	25	16	2.06	<0.01	11	1.10	881	<1	45	579	92	1.60	<5	<5	<10	192	2026	4	40	<10	8	217
196323D	1365095	0.092	3	5.19	22	510	<2	<1	1.81	<4	9	23	15	2.09	<0.01	14	1.15	896	<1	43	607	68	1.63	<5	<5	<10	205	2263	4	42	<10	8	145
196324	1365096	0.076	2	5.13	24	511	<2	<1	1.82	<4	10	26	15	2.08	<0.01	14	1.12	860	<1	43	575	61	1.61	<5	<5	<10	209	2134	4	42	<10	8	120
196325	1365097	0.017	1	3.93	8	454	<2	1	1.42	<4	8	18	14	1.92	<0.01	12	0.97	641	<1	31	562	17	0.79	<5	<5	<10	185	2334	3	43	<10	7	53
196326	1365098	0.009	1	4.61	3	541	<2	<1	1.14	<4	9	49	9	1.11	<0.01	12	0.63	278	<1	54	434	17	0.69	<5	<5	<10	216	1772	2	37	<10	7	26
196327	1365099	0.008	<1	4.75	6	453	<2	<1	1.20	<4	5	28	4	0.65	<0.01	8	0.53	177	<1	35	375	14	0.57	<5	<5	<10	219	1507	4	28	<10	5	5
196328	1365100	1.808	<1	4.35	2	398	<2	3	1.98	<4	15	48	31	3.51	<0.01	10	1.24	658	<1	34	615	7	0.33	<5	<5	<10	262	2683	4	110	18	18	48
196329	1365101	0.012	1	5.31	6	488	<2	1	1.08	<4	8	16	11	0.88	<0.01	10	0.56	196	<1	46	398	13	0.48	<5	<5	<10	242	1773	3	36	<10	6	10
196330	1365102	0.056	1	5.97	11	555	<2	<1	1.25	<4	7	77	7	0.77	<0.01	14	0.53	171	<1	62	405	14	0.57	<5	<5	<10	255	1798	3	33	<10	5	13
196331	1365103	0.010	1	6.02	10	537	<2	<1	1.48	<4	7	29	11	0.77	<0.01	11	0.42	161	<1	61	403	16	0.64	<5	<5	<10	275	1656	3	28	<10	5	14
196332	1365104	0.008	2	5.01	10	475	<2	2	1.48	<4	7	34	6	0.92	<0.01	10	0.42	206	<1	70	398	11	0.78	<5	<5	<10	239	1592	<2	27	<10	6	21

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, August 9, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/10/2012
 Date Completed: 07/27/2012
 Job #: 201242628
 Reference: TL 12 275
 Sample #: 100

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
196333	1365105	0.006	1	3.75	2	494	<2	10	1.15	<4	7	25	7	0.77	<0.01	6	0.41	156	<1	52	416	8	0.55	<5	<5	<10	221	1481	<2	26	<10	5	18
196334D	1365105	0.006	2	5.32	6	554	<2	5	1.43	<4	7	26	7	0.79	<0.01	9	0.46	160	<1	49	419	10	0.61	<5	<5	<10	254	1622	<2	28	<10	5	20
196335	1365106	0.012	<1	5.62	6	516	<2	<1	1.28	<4	4	23	9	0.73	<0.01	10	0.48	166	<1	40	466	14	0.73	<5	<5	<10	234	1605	2	28	<10	6	24
196336	1365107	0.010	1	5.44	6	603	<2	<1	1.45	<4	4	30	6	0.85	<0.01	9	0.53	232	<1	52	430	13	0.65	<5	<5	<10	231	1709	3	31	<10	6	23
196337	1365108	0.012	4	4.28	20	518	16	13	1.24	15	19	27	9	0.84	<0.01	7	0.41	239	<1	50	380	14	0.73	<5	6	<10	202	1393	11	42	<10	26	77
196338	1365109	0.009	2	4.95	6	485	<2	1	0.93	<4	5	31	3	0.89	<0.01	12	0.55	255	<1	54	421	17	0.70	<5	<5	<10	157	1705	<2	29	<10	6	22
196339	1365110	0.006	2	4.71	5	422	<2	2	2.21	<4	16	52	22	3.30	<0.01	9	1.35	685	<1	38	626	12	0.35	<5	<5	<10	287	2950	9	112	17	19	44
196340	1365111	0.025	1	5.87	22	539	<2	2	2.41	<4	9	36	8	1.96	<0.01	14	1.24	740	<1	61	486	42	1.23	<5	<5	<10	238	2104	<2	46	<10	9	117
196341	1365112	0.018	2	7.32	12	567	<2	4	1.67	<4	12	19	10	1.21	<0.01	17	0.94	654	<1	43	482	41	0.72	<5	<5	<10	265	2112	10	35	<10	7	56
196342	1365113	0.053	2	6.26	33	502	<2	<1	1.35	<4	7	38	11	1.31	<0.01	15	0.81	794	<1	50	396	56	1.13	<5	<5	<10	198	1810	2	34	<10	8	263
196343	1365114	0.020	2	5.88	16	479	<2	2	1.02	<4	6	36	6	1.04	<0.01	15	0.72	547	<1	51	393	28	0.77	<5	<5	<10	174	1787	2	31	<10	6	35
196344	1365115	0.025	1	6.74	26	464	<2	<1	1.44	<4	7	28	5	1.00	<0.01	15	0.76	576	<1	43	425	23	0.80	<5	<5	<10	205	1750	<2	33	<10	7	17
196345D	1365115	0.026	1	6.53	21	470	<2	1	1.38	<4	7	29	6	0.98	<0.01	15	0.76	559	<1	45	415	15	0.85	<5	<5	<10	196	1702	4	32	<10	7	16
196346	1365116	0.025	2	7.11	22	506	<2	<1	1.48	<4	7	33	7	1.09	<0.01	16	0.81	589	<1	54	439	20	0.92	<5	<5	<10	209	1753	2	33	<10	7	18
196347	1365117	0.027	1	6.44	17	434	<2	<1	1.21	<4	8	33	2	1.13	<0.01	14	0.78	678	<1	59	418	38	0.93	<5	<5	<10	207	1726	10	29	<10	6	25
196348	1365118	0.082	3	6.36	28	412	<2	5	1.15	<4	9	29	7	1.26	<0.01	14	0.76	722	<1	55	436	85	1.10	<5	<5	<10	213	1679	2	30	<10	7	246
196349	1365119	0.036	1	4.05	12	366	<2	3	0.72	<4	7	32	9	0.88	<0.01	7	0.56	551	<1	61	416	73	0.59	<5	<5	<10	173	1571	<2	29	<10	5	52
196350	1365120	0.214	2	0.86	395	4690	<2	4	0.78	<4	6	20	33	2.81	<0.01	6	0.30	100	<1	20	126	28	0.72	14	<5	<10	157	999	3	16	39	11	18
196351	1365121	0.055	12	6.16	32	751	<2	<1	0.87	20	8	37	162	1.78	<0.01	15	0.64	516	<1	72	372	2500	1.64	9	5	<10	202	1543	3	30	48	7	6391
196352	1365122	0.010	3	6.81	8	320	<2	4	0.91	<4	7	38	15	0.82	<0.01	13	0.68	460	<1	71	388	223	0.63	<5	<5	<10	204	1569	<2	29	<10	6	304

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, August 9, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/10/2012
 Date Completed: 07/27/2012
 Job #: 201242628
 Reference: TL 12 275
 Sample #: 100

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
196353	1365123	0.051	3	7.29	14	352	<2	<1	1.16	<4	7	34	7	0.94	<0.01	16	0.84	590	<1	58	429	381	0.75	<5	<5	<10	202	1768	<2	32	<10	7	643
196354	1365124	0.021	2	6.22	16	336	<2	6	1.19	<4	8	36	9	0.98	<0.01	17	0.91	669	<1	67	415	64	0.73	<5	<5	<10	191	1693	8	29	<10	7	81
196355	1365125	0.023	2	6.47	11	394	<2	<1	0.75	<4	5	37	21	0.98	<0.01	18	0.69	367	<1	59	425	49	0.88	<5	<5	<10	197	1855	2	28	<10	7	23
196356D	1365125	0.017	1	6.46	13	369	<2	<1	0.64	<4	6	39	22	0.98	<0.01	16	0.67	352	<1	62	441	50	0.89	<5	<5	<10	180	1751	<2	27	<10	7	23
196357	1365126	0.021	2	7.20	17	373	<2	2	1.42	<4	6	33	11	1.22	<0.01	17	0.85	533	<1	54	434	23	1.11	<5	<5	<10	207	1868	3	31	<10	8	33
196358	1365127	0.027	<1	6.96	17	365	<2	2	1.79	<4	8	27	11	1.49	<0.01	17	1.03	833	<1	44	400	25	1.21	<5	<5	<10	221	1774	5	29	<10	7	33
196359	1365128	0.369	1	6.25	27	431	<2	<1	0.68	<4	6	37	10	1.48	<0.01	13	0.77	510	<1	67	397	46	1.32	<5	<5	<10	168	1801	<2	28	<10	7	74
196360	1365129	1.333	<1	6.74	31	441	<2	1	0.59	<4	7	41	5	1.69	<0.01	16	0.76	507	<1	77	404	35	1.61	<5	<5	<10	175	1834	3	29	<10	8	42
196361	1365130	0.008	1	5.87	2	434	<2	6	2.39	<4	17	55	24	3.54	<0.01	12	1.41	737	<1	38	649	7	0.47	<5	<5	<10	310	3194	2	117	17	21	48
196362	1365131	0.311	1	3.19	29	301	<2	<1	1.55	<4	6	23	6	1.51	<0.01	8	1.25	1028	<1	47	603	34	0.77	<5	<5	<10	201	1587	8	21	<10	5	109
196363	1365132	0.016	1	0.09	11	208	<2	2	0.81	<4	4	15	8	1.55	<0.01	4	0.90	841	<1	27	395	29	0.76	<5	<5	<10	114	1387	<2	23	<10	4	85
196364	1365133	0.269	10	1.45	19	271	<2	5	0.16	<4	6	24	21	1.62	<0.01	3	0.39	291	<1	46	397	168	1.39	<5	<5	<10	115	1436	6	23	<10	5	227
196365	1365134	0.011	3	3.15	17	291	<2	1	1.00	<4	7	17	7	1.65	<0.01	10	0.68	581	<1	30	420	28	0.99	<5	<5	<10	165	1833	4	28	<10	6	63
196366	1365135	0.007	3	3.85	7	273	<2	1	2.30	<4	13	20	4	1.45	<0.01	9	0.69	507	<1	43	433	13	0.69	<5	<5	<10	244	1624	3	29	<10	6	391
196367D	1365135	0.006	2	3.81	9	271	<2	2	2.37	<4	14	22	4	1.38	<0.01	8	0.64	473	<1	49	411	17	0.63	<5	<5	<10	255	1516	<2	28	<10	6	394
196368	1365136	0.007	2	3.71	3	273	<2	<1	2.30	<4	13	39	5	1.51	<0.01	7	0.64	481	<1	82	436	17	0.60	<5	5	<10	249	1485	3	29	<10	6	446
196369	1365137	0.011	1	3.11	31	320	<2	2	2.00	<4	11	21	4	1.52	<0.01	3	0.52	455	<1	51	425	19	1.46	<5	<5	<10	244	1451	2	27	<10	5	165
196370	1365138	0.008	4	4.25	1583	387	<2	51	1.23	39	7	27	2887	1.87	<0.01	5	0.36	301	7	54	383	1283	2.52	<5	<5	173	246	891	2	25	115	19	38
196371	1365139	0.016	1	2.70	13	377	<2	2	0.14	<4	6	14	<1	1.29	<0.01	8	0.32	174	<1	29	365	10	1.63	<5	<5	<10	236	770	2	21	<10	5	56
196372	1365140		74	2.60	33	429	<2	1	1.08	23	15	33	55	3.38	<0.01	5	0.81	502	<1	29	580	589	0.77	40	<5	246	235	1860	3	89	41	15	1720

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, August 9, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/10/2012
 Date Completed: 07/27/2012
 Job #: 201242628
 Reference: TL 12 275
 Sample #: 100

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
196373	1365141	0.014	2	4.04	25	566	<2	<1	0.48	<4	8	27	32	1.58	<0.01	5	0.51	232	<1	43	401	29	1.51	<5	<5	<10	269	1110	2	29	<10	6	120
196374	1365142	0.023	2	3.63	4	483	<2	<1	1.08	<4	20	123	46	3.51	<0.01	18	1.35	518	<1	92	532	16	1.30	<5	<5	<10	217	2209	3	81	<10	13	141
196375	1365143	0.014	1	4.64	12	616	<2	<1	1.82	<4	10	37	15	2.26	<0.01	16	1.19	511	<1	46	599	34	1.08	<5	5	<10	306	2040	2	45	<10	8	79
196376	1365144	0.134	2	4.27	20	576	<2	<1	0.67	4	9	21	50	1.80	<0.01	13	0.71	307	<1	37	648	320	1.67	<5	<5	<10	226	1888	<2	36	12	7	841
196377	1365145	0.006	2	4.79	4	568	<2	5	1.59	<4	9	18	7	2.05	<0.01	18	1.03	411	<1	32	659	42	0.60	<5	<5	<10	239	2414	6	42	<10	8	101
196378R	1365145	0.007	1	2.84	7	436	<2	1	1.20	<4	9	19	3	2.03	<0.01	17	1.05	422	<1	32	651	18	0.50	<5	<5	<10	165	2323	4	40	<10	8	42
196379	1365146	0.044	3	5.94	19	590	<2	<1	1.78	<4	10	32	11	2.07	<0.01	13	1.10	1192	<1	51	584	62	1.33	<5	<5	<10	217	1990	7	42	<10	9	86
196380	1365147	0.023	3	6.25	29	535	<2	2	0.69	<4	10	40	18	1.84	0.06	7	0.76	557	<1	64	583	97	1.48	<5	<5	<10	197	2002	6	44	<10	8	102
196381	1365148	0.237	4	5.24	25	406	2	<1	0.12	<4	8	27	42	1.86	<0.01	3	0.44	211	<1	49	497	213	2.02	<5	<5	<10	133	1515	4	37	11	8	461
196382	1365149	0.677	21	4.98	14	432	<2	<1	<0.01	5	7	34	51	1.74	<0.01	2	0.37	110	<1	62	440	349	1.91	8	<5	<10	119	1377	3	36	16	7	1274
196383	1365150	<0.005	3	3.37	2	404	<2	<1	1.96	<4	17	51	26	3.36	<0.01	4	1.28	672	<1	38	617	35	0.34	<5	<5	<10	268	2833	2	111	20	18	132
196384	1365151	0.309	3	4.09	17	418	<2	<1	1.05	<4	8	34	38	1.91	<0.01	2	0.89	474	<1	50	489	84	1.37	<5	<5	<10	154	1458	2	43	10	8	161
196385	1365152	0.035	2	4.19	12	395	2	1	1.41	<4	7	35	19	1.85	<0.01	6	1.08	689	<1	62	527	64	0.83	<5	<5	<10	144	1591	2	37	<10	7	89
196386	1365153	0.936	2	1.75	14	358	<2	<1	0.24	<4	6	35	23	1.37	<0.01	<1	0.50	268	<1	64	470	66	1.00	<5	<5	<10	92	1083	<2	29	<10	6	214
196387	1365154	0.416	1	1.44	14	296	<2	1	<0.01	<4	6	36	27	1.08	<0.01	<1	0.23	<100	<1	66	383	56	0.96	<5	<5	<10	70	986	<2	26	<10	5	220
196388	1365155	0.032	1	3.07	11	405	<2	<1	<0.01	<4	6	33	12	1.02	<0.01	<1	0.37	175	<1	59	469	53	0.76	<5	<5	<10	87	1369	5	32	<10	7	105
196389D	1365155	0.047	2	4.14	19	426	<2	<1	0.10	<4	8	31	11	1.02	<0.01	3	0.43	188	<1	51	498	60	0.81	<5	<5	<10	95	1496	<2	34	<10	7	98
196390	1365156	0.041	1	3.74	20	417	<2	<1	0.04	<4	8	28	11	1.01	<0.01	2	0.42	182	<1	49	472	64	0.79	<5	<5	<10	89	1448	<2	33	<10	7	119
196391	1365157	0.029	1	4.84	22	473	<2	<1	1.15	<4	10	27	12	1.75	<0.01	7	0.90	536	<1	46	506	65	1.01	<5	<5	<10	119	1922	4	39	<10	7	92
196392	1365158	0.006	2	5.51	2	444	<2	4	2.12	<4	7	28	5	1.83	0.02	15	1.28	778	<1	46	525	48	0.47	<5	<5	<10	137	2200	10	42	<10	7	104

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, August 9, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/10/2012
 Date Completed: 07/27/2012
 Job #: 201242628
 Reference: TL 12 275
 Sample #: 100

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
196393	1365159	0.020	1	5.80	16	559	<2	<1	0.39	<4	10	30	4	1.79	<0.01	6	0.52	219	<1	52	512	47	1.58	<5	<5	<10	100	2336	<2	42	<10	7	52
196394	1365160	1.950	2	4.60	3	450	<2	3	2.03	<4	18	52	33	3.85	<0.01	9	1.30	720	<1	40	667	16	0.35	<5	<5	<10	271	3101	<2	120	20	19	56
196395	1365161	0.026	3	5.62	<2	570	<2	<1	1.70	<4	10	33	12	2.03	<0.01	17	1.14	581	<1	44	539	48	1.03	<5	<5	<10	165	2334	6	48	<10	8	63
196396	1365162	0.312	3	4.93	47	337	2	1	1.06	6	21	122	60	3.34	<0.01	11	0.88	523	<1	88	518	204	2.75	<5	<5	<10	85	2712	<2	77	<10	16	774
196397	1365163	0.398	1	4.71	18	270	2	<1	1.56	<4	17	111	46	2.98	<0.01	15	1.17	707	<1	75	493	46	1.43	<5	<5	<10	88	2609	<2	73	<10	16	97
196398	1365164	1.574	5	4.17	93	250	<2	3	0.09	6	15	111	108	2.87	<0.01	7	0.48	146	<1	79	401	726	3.44	16	<5	<10	58	1740	4	62	13	13	1219
196399	1365165	0.313	3	5.68	76	288	2	<1	1.21	<4	15	98	53	3.09	<0.01	14	0.95	525	<1	70	501	119	2.74	<5	5	<10	94	2096	<2	64	<10	16	207
196400D	1365165	0.267	1	5.93	72	301	2	4	1.38	<4	17	96	47	3.09	<0.01	15	1.07	596	<1	66	511	56	2.60	<5	<5	<10	98	2223	6	66	<10	16	98
196401	1365166	0.284	<1	6.50	44	338	2	<1	0.88	4	26	137	65	4.14	0.11	19	1.07	578	<1	108	539	55	2.74	<5	<5	<10	97	3049	3	101	<10	20	92
196402	1365167	0.189	1	6.04	69	381	2	<1	1.10	<4	20	116	60	3.05	0.15	17	0.99	468	<1	81	612	77	2.19	<5	<5	<10	109	2925	4	81	10	19	261
196403	1365168	0.555	2	4.84	73	315	2	<1	0.61	<4	15	88	61	2.32	<0.01	11	0.71	297	<1	75	494	131	2.11	<5	<5	<10	101	2199	3	61	<10	12	209
196404	1365169	0.186	3	4.16	16	276	2	<1	0.84	<4	13	98	100	2.21	<0.01	12	0.97	422	<1	88	501	287	1.22	<5	<5	<10	90	2424	4	59	<10	13	466
196405	1365170	0.011	3	3.55	<2	377	<2	4	2.03	<4	15	57	30	3.33	<0.01	6	1.31	681	<1	40	616	29	0.30	<5	<5	<10	262	3024	2	110	16	18	82
196406	1365171	0.054	1	3.63	5	310	2	6	1.30	<4	23	159	49	3.76	<0.01	14	1.41	674	<1	135	554	44	0.69	<5	<5	<10	131	3101	3	95	<10	17	89
196407	1365172	0.027	3	5.01	3	287	2	<1	1.67	4	25	178	56	3.95	<0.01	21	1.49	734	<1	152	580	35	0.70	<5	<5	<10	120	3297	6	95	<10	19	69
196408	1365173	0.164	2	5.46	<2	288	2	5	1.29	<4	24	151	54	3.60	<0.01	21	1.32	699	<1	108	591	50	1.11	<5	<5	<10	100	3353	4	99	<10	17	84
196409	1365174	0.712	3	5.82	11	284	2	1	1.23	4	24	155	76	3.92	<0.01	22	1.26	637	<1	111	580	164	1.51	<5	<5	<10	107	3499	4	107	10	19	255
196410	1365175	0.035	2	3.32	13	432	<2	2	1.02	<4	6	58	23	1.73	<0.01	15	1.10	380	<1	97	251	39	1.02	<5	<5	<10	113	1253	9	26	<10	7	282
196411D	1365175	0.032	<1	4.31	20	521	<2	3	1.25	<4	4	58	19	1.66	<0.01	18	1.21	398	<1	107	238	37	1.01	<5	<5	<10	137	1129	7	21	<10	6	304
196412	1365176	0.036	<1	5.04	18	572	<2	5	1.10	<4	5	23	23	1.47	<0.01	20	1.12	329	<1	41	242	34	1.14	<5	<5	<10	141	1162	4	19	<10	6	294

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, August 9, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/10/2012
 Date Completed: 07/27/2012
 Job #: 201242628
 Reference: TL 12 275
 Sample #: 100

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
196413	1365177	0.093	1	3.39	19	376	<2	<1	0.58	<4	4	42	6	1.48	<0.01	16	1.27	330	<1	83	236	24	0.86	<5	<5	<10	104	1114	5	18	<10	4	210
196414	1365178	0.018	<1	5.20	6	334	<2	<1	0.91	<4	4	31	2	1.21	<0.01	18	1.35	365	<1	58	246	22	0.58	<5	5	<10	126	1215	10	19	<10	6	56
196415	1365179	0.081	2	4.10	19	277	<2	5	0.74	8	3	28	52	1.51	<0.01	16	1.24	394	<1	47	273	108	1.33	<5	<5	<10	94	1083	<2	17	16	5	1643
196416	1365180	0.273	<1	<0.01	364	4576	<2	3	0.72	4	7	93	38	2.96	<0.01	3	0.35	108	<1	52	115	35	0.72	16	<5	<10	146	1103	7	16	42	10	158
196417	1365181	0.064	2	5.13	35	824	<2	<1	0.94	<4	5	68	9	1.61	<0.01	18	1.18	352	<1	114	251	29	0.61	<5	<5	<10	118	1311	2	22	<10	6	41
196418	1365182	0.286	2	4.69	22	290	<2	<1	1.81	18	3	43	21	2.36	<0.01	19	1.79	776	<1	81	254	437	2.25	<5	<5	<10	123	1067	5	19	36	6	3811
196419	1365183	0.029	<1	6.70	12	329	<2	3	1.72	<4	4	101	10	1.62	<0.01	27	1.74	678	<1	92	280	114	0.97	<5	<5	<10	132	1266	4	22	<10	7	472
196420	1365184	0.033	<1	4.24	54	320	<2	<1	0.98	<4	5	36	70	1.26	<0.01	16	1.32	430	<1	56	246	77	0.81	<5	<5	<10	102	1172	6	18	<10	6	327
196421	1365185	0.115	1	5.01	31	354	<2	6	1.24	<4	4	48	69	1.75	<0.01	16	1.62	533	<1	85	265	305	1.24	<5	<5	<10	110	1207	4	21	<10	6	496
196422D	1365185	0.122	2	5.01	53	362	<2	4	1.23	4	4	42	97	1.69	<0.01	16	1.65	521	<1	64	257	351	1.28	<5	<5	<10	107	1165	17	20	11	6	641

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/04/2012
 Date Completed:
 Job #: 201242542
 Reference: TL 12 276
 Sample #: 79

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
189955	1361389	0.017	<1	2.74	12	471	<2	13	0.78	<4	7	25	6	1.58	<0.01	9	0.57	433	<1	51	455	15	0.84	<5	7	<10	149	1721	<2	36	<10	6	48
189956	1361390	0.009	<1	3.07	24	374	<2	15	1.95	<4	14	43	18	2.80	<0.01	6	1.21	573	<1	29	501	10	0.29	<5	<5	<10	252	2463	5	100	18	14	43
189957	1361391	0.009	<1	2.82	19	397	<2	14	0.95	<4	7	21	5	0.60	<0.01	8	0.55	168	<1	43	336	15	0.31	<5	6	<10	180	1271	<2	25	<10	4	28
189958	1361392	0.007	<1	2.38	15	385	<2	6	1.02	<4	6	22	7	0.57	<0.01	5	0.51	147	<1	40	305	14	0.30	<5	8	<10	202	1155	<2	24	<10	4	29
189959	1361393	0.007	<1	2.92	11	461	<2	7	0.83	<4	6	22	6	0.52	<0.01	8	0.49	117	<1	41	300	14	0.33	<5	8	<10	215	1239	<2	26	<10	4	23
189960	1361394	0.009	<1	1.86	14	379	<2	10	0.44	<4	6	21	2	0.49	<0.01	5	0.32	<100	<1	41	321	13	0.41	<5	6	<10	156	1242	<2	24	<10	4	15
189961	1361395	0.006	<1	1.10	10	338	<2	19	0.60	<4	5	18	3	0.42	<0.01	2	0.29	110	<1	41	303	17	0.31	<5	<5	<10	155	1147	2	22	<10	3	72
189962	1361396	0.006	<1	2.70	30	381	<2	14	0.87	<4	6	23	4	0.46	<0.01	6	0.32	113	<1	47	312	16	0.39	<5	<5	<10	194	1222	<2	23	<10	4	61
189963	1361397	0.009	<1	2.45	29	401	<2	12	0.76	<4	3	20	7	0.59	<0.01	5	0.35	119	<1	42	293	9	0.43	<5	<5	<10	187	1133	<2	23	<10	4	35
189964	1361398	0.006	<1	2.93	212	420	<2	27	0.92	5	4	27	334	0.68	<0.01	6	0.40	138	<1	49	278	177	0.47	<5	6	32	208	1146	<2	23	15	5	1242
189965D	1361398	0.007	<1	3.49	16	426	<2	16	0.93	<4	5	26	14	0.61	<0.01	8	0.43	137	<1	47	299	20	0.39	<5	<5	<10	207	1213	<2	24	<10	5	50
189966	1361399	0.006	<1	3.48	26	458	<2	37	0.85	<4	4	32	5	0.65	<0.01	8	0.40	141	<1	59	320	16	0.38	<5	<5	<10	193	1190	<2	25	<10	4	29
189967	1361400	4.780	56	2.39	50	393	<2	7	1.04	17	12	26	44	2.73	<0.01	6	0.77	410	<1	22	437	486	0.61	47	11	196	203	1586	<2	77	46	11	1577
189968	1361401	0.051	<1	2.51	18	383	<2	14	1.21	<4	7	26	59	1.40	<0.01	10	0.72	399	<1	45	358	45	0.55	<5	5	<10	169	1400	<2	31	<10	5	166
189969	1361402	0.030	<1	3.57	29	336	<2	12	1.44	<4	5	26	11	1.03	<0.01	7	0.63	370	<1	45	290	27	0.71	<5	6	<10	116	1144	<2	23	<10	5	55
189970	1361403	0.047	<1	3.55	36	398	<2	17	1.62	<4	4	35	8	1.29	<0.01	6	0.67	467	<1	67	300	20	0.82	<5	<5	<10	111	1128	<2	23	<10	5	46
189971	1361404	0.120	<1	3.59	31	396	<2	14	1.26	<4	5	22	20	1.13	<0.01	6	0.60	395	<1	40	281	46	0.94	<5	8	<10	113	1180	<2	24	<10	5	60
189972	1361405	0.561	4	3.38	38	467	<2	14	0.34	<4	5	27	11	1.12	<0.01	6	0.52	223	<1	49	281	138	1.09	<5	8	<10	83	1250	<2	24	<10	5	358
189973	1361406	0.115	2	3.77	45	523	<2	22	0.39	<4	5	23	7	1.05	<0.01	7	0.57	272	<1	46	348	27	0.97	<5	<5	<10	80	1373	2	25	<10	5	50
189974	1361407	0.398	6	2.53	25	385	<2	26	0.40	<4	5	32	7	1.01	<0.01	5	0.54	269	<1	51	272	34	0.89	<5	6	<10	80	1179	<2	24	<10	5	89

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/04/2012
 Date Completed:
 Job #: 201242542
 Reference: TL 12 276
 Sample #: 79

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
189975	1361408	0.202	3	3.60	34	294	<2	5	1.11	<4	4	21	74	1.23	0.30	8	0.69	531	<1	37	289	78	0.89	<5	6	<10	87	1035	<2	18	<10	4	272
189976D	1361408	0.196	3	4.11	38	471	<2	16	1.53	<4	7	28	81	1.68	<0.01	10	1.01	724	<1	56	422	108	1.38	<5	6	<10	137	1452	3	28	<10	6	208
189977	1361409	0.115	<1	3.44	39	399	<2	13	0.99	<4	7	27	25	1.25	<0.01	10	0.72	541	<1	59	434	72	1.01	<5	7	<10	117	1510	<2	27	<10	5	112
189978	1361410	<0.005	<1	2.94	14	334	<2	15	1.85	<4	15	40	17	2.73	<0.01	6	1.18	556	<1	24	483	8	0.30	<5	6	<10	234	2411	2	95	11	14	45
189979	1361411	0.078	<1	3.15	39	368	<2	11	0.83	<4	6	14	7	0.97	<0.01	7	0.58	453	<1	32	390	39	0.74	<5	5	<10	110	1374	<2	26	<10	5	83
189980	1361412	0.031	<1	2.04	27	309	<2	2	0.97	<4	6	25	15	1.17	<0.01	8	0.72	655	<1	48	430	33	0.66	<5	5	<10	111	1475	<2	28	<10	5	116
189981	1361413	0.028	<1	2.27	31	377	<2	18	1.27	<4	5	43	7	1.14	<0.01	5	0.84	685	<1	82	403	21	0.58	<5	5	<10	134	1348	<2	28	<10	5	50
189982	1361414	0.058	3	2.26	14	398	2	17	1.16	<4	5	35	28	1.27	<0.01	5	0.88	646	<1	43	355	441	0.83	<5	<5	<10	117	1315	<2	26	<10	4	400
189983	1361415	0.049	<1	3.61	23	444	<2	17	0.87	<4	5	26	15	1.16	<0.01	11	0.69	547	<1	35	342	133	0.96	<5	<5	<10	130	1474	<2	29	<10	5	93
189984	1361416	0.065	<1	3.04	34	413	<2	14	0.68	<4	5	25	14	1.04	<0.01	9	0.61	454	<1	32	320	137	0.87	<5	5	<10	113	1407	4	27	<10	4	177
189985	1361417	0.082	1	2.45	29	397	<2	14	0.54	<4	6	22	14	0.97	<0.01	8	0.58	422	<1	36	366	82	0.73	<5	9	<10	107	1467	<2	28	<10	4	100
189986	1361418	6.475	6	3.16	65	325	<2	15	0.66	<4	5	27	30	0.97	<0.01	9	0.67	425	<1	43	251	212	0.81	<5	<5	<10	119	1181	<2	22	<10	4	360
189987D	1361418	7.314	6	3.35	75	327	<2	14	0.69	<4	4	26	31	0.98	<0.01	10	0.69	433	<1	43	252	218	0.83	<5	8	<10	122	1198	<2	22	<10	4	363
189988	1361419	0.313	<1	3.18	33	292	<2	12	0.93	<4	5	34	2	0.73	<0.01	10	0.86	594	<1	59	293	37	0.47	<5	<5	<10	122	1204	<2	23	<10	4	47
189989	1361420	1.919	<1	2.73	18	364	<2	26	1.78	<4	15	42	25	3.10	<0.01	6	1.22	598	<1	27	504	14	0.30	<5	<5	<10	226	2333	<2	101	15	13	47
189990	1361421	0.030	<1	2.38	34	289	<2	23	0.27	<4	8	20	4	0.73	<0.01	8	0.64	372	<1	40	289	34	0.58	<5	7	<10	79	1252	<2	23	<10	4	475
189991	1361422	0.029	<1	2.89	30	253	<2	30	0.60	<4	6	29	6	0.94	<0.01	10	0.65	418	<1	49	331	16	0.82	<5	<5	<10	85	1332	<2	25	<10	4	30
189992	1361423	0.025	<1	3.31	21	246	<2	37	0.64	<4	5	25	7	0.75	<0.01	10	0.71	426	<1	40	305	17	0.56	<5	5	<10	90	1382	<2	26	<10	5	43
189993	1361424	0.016	<1	3.28	21	236	<2	17	1.09	<4	4	29	7	0.94	<0.01	7	0.73	496	<1	50	313	22	0.54	<5	9	<10	99	1313	3	25	<10	4	34
189994	1361425	0.013	<1	3.18	41	268	<2	22	1.93	<4	9	32	12	1.33	<0.01	6	0.57	446	<1	58	307	19	0.87	<5	8	<10	201	1065	<2	23	<10	5	34

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/04/2012
 Date Completed:
 Job #: 201242542
 Reference: TL 12 276
 Sample #: 79

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
189995	1361426	0.015	<1	3.21	49	310	<2	11	0.95	<4	13	20	7	1.77	<0.01	7	0.41	195	<1	43	294	24	1.94	<5	<5	<10	187	1244	<2	23	<10	4	87
189996	1361427	0.016	<1	3.18	42	296	<2	12	1.68	<4	10	33	9	1.93	<0.01	6	0.44	271	<1	62	291	18	2.14	<5	<5	<10	197	1126	<2	24	<10	5	200
189997	1361428	0.019	<1	3.28	37	300	<2	15	1.85	<4	12	20	4	3.15	<0.01	5	0.64	351	<1	45	292	19	3.63	<5	<5	<10	208	1121	<2	23	<10	5	383
189998D	1361428	0.020	<1	2.78	37	280	<2	16	1.69	<4	11	19	3	2.98	<0.01	4	0.61	326	<1	45	271	18	3.45	<5	5	<10	195	1034	<2	22	<10	4	358
189999	1361429	0.013	<1	3.45	30	299	<2	21	1.91	<4	9	36	3	1.68	<0.01	8	0.92	434	<1	64	287	16	1.57	<5	<5	<10	209	1147	<2	24	<10	4	193
190000	1361430	0.009	<1	3.25	15	371	<2	22	1.98	<4	14	42	17	2.79	<0.01	6	1.23	573	<1	25	497	8	0.32	<5	<5	<10	255	2419	<2	99	14	14	41
190001	1361431	0.009	<1	4.25	22	323	<2	22	1.60	<4	8	21	4	0.99	<0.01	9	0.56	221	<1	39	316	16	1.10	<5	<5	<10	214	1205	3	25	<10	5	46
190002	1361432	0.016	<1	4.85	33	376	<2	13	0.97	<4	6	34	2	1.21	<0.01	14	0.85	278	<1	58	315	11	1.29	<5	<5	<10	191	1340	<2	25	<10	5	111
190003	1361433	0.010	<1	4.64	30	426	<2	11	0.76	<4	5	29	1	1.67	<0.01	13	0.71	189	<1	53	299	11	1.77	<5	6	<10	223	1376	4	25	<10	5	84
190004	1361434	0.019	<1	4.52	20	363	<2	10	2.10	<4	8	34	11	2.31	<0.01	18	1.32	550	<1	44	545	10	1.49	<5	<5	<10	276	1608	<2	40	<10	8	49
190005	1361435	0.018	<1	4.86	17	422	<2	<1	1.79	<4	9	32	6	1.86	<0.01	15	1.00	427	<1	46	450	19	0.76	<5	5	<10	192	1638	2	37	<10	7	47
190006	1361436	0.013	<1	4.71	14	412	<2	9	1.86	<4	8	24	5	1.80	<0.01	14	0.99	422	<1	38	475	23	0.67	<5	<5	11	197	1629	<2	36	<10	6	45
190007	1361437	0.005	<1	<0.01	12	30	<2	8	0.19	<4	2	67	3	0.54	<0.01	<1	0.27	<100	2	86	<100	6	0.43	<5	<5	<10	64	306	<2	8	<10	4	10
190008	1361438	0.026	1	7.17	13	682	2	16	3.58	<4	19	203	74	3.45	<0.01	21	1.42	814	<1	80	235	27	1.51	<5	<5	<10	376	3076	<2	94	<10	13	153
190009D	1361438	0.033	1	7.47	20	698	2	11	3.63	<4	20	201	73	3.40	<0.01	25	1.38	801	<1	80	237	26	1.57	<5	<5	<10	379	3069	<2	94	<10	12	151
190010	1361439	0.010	<1	0.96	14	102	<2	19	0.27	<4	2	53	5	0.57	<0.01	3	0.32	<100	<1	63	121	11	0.49	<5	<5	<10	78	527	<2	13	<10	5	13
190011	1361440	0.228	<1	<0.01	352	>5000	<2	12	0.65	<4	6	12	23	2.28	<0.01	3	0.24	<100	<1	10	<100	17	0.68	14	<5	<10	108	648	6	12	37	8	15
190012	1361441	0.035	1	6.51	30	735	2	21	2.27	<4	19	108	31	2.97	<0.01	17	1.10	631	<1	78	478	30	1.62	<5	8	<10	270	2409	<2	75	<10	12	78
190013	1361442	0.017	<1	5.19	18	480	<2	20	2.04	<4	13	89	21	2.35	<0.01	12	1.06	585	<1	68	434	26	1.34	<5	<5	<10	207	1862	<2	60	<10	11	57
190014	1361443	0.008	<1	0.85	25	59	<2	6	0.93	<4	6	78	15	1.27	<0.01	3	0.59	250	<1	83	144	8	0.77	<5	5	<10	86	832	<2	22	<10	6	30

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/04/2012
 Date Completed:
 Job #: 201242542
 Reference: TL 12 276
 Sample #: 79

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
190015	1361444	0.016	1	4.90	13	432	2	20	2.43	<4	13	78	37	2.51	<0.01	12	1.16	609	<1	72	439	28	1.11	<5	<5	<10	184	2035	<2	56	<10	9	63
190016	1361445	0.013	2	4.67	46	289	<2	10	1.42	<4	7	27	12	1.57	<0.01	11	0.96	652	<1	45	438	37	0.96	<5	9	<10	112	1726	<2	35	<10	6	68
190017	1361446	0.145	29	5.27	47	254	<2	10	0.12	<4	10	23	18	1.28	<0.01	6	0.38	126	<1	51	418	60	1.29	<5	9	<10	81	1675	<2	33	<10	7	560
190018	1361447	0.060	8	5.40	44	281	<2	24	0.12	<4	8	26	10	1.55	<0.01	6	0.38	111	<1	48	381	40	1.73	<5	9	<10	76	1562	<2	32	<10	6	650
190019	1361448	0.008	<1	6.02	19	389	2	17	1.97	<4	7	28	8	1.49	<0.01	13	1.23	647	<1	47	457	43	0.68	<5	<5	<10	118	1690	5	38	<10	7	116
190020R	1361448	0.009	<1	4.51	21	358	<2	21	1.71	<4	6	27	7	1.43	<0.01	9	1.13	603	<1	50	420	43	0.59	<5	5	<10	103	1468	<2	34	<10	6	88
190021	1361449	0.009	<1	5.24	21	354	<2	10	2.04	<4	7	16	5	1.45	<0.01	11	1.23	579	<1	28	412	41	0.79	<5	<5	<10	119	1497	<2	32	<10	6	80
190022	1361450	0.011	<1	3.05	24	350	<2	14	1.83	<4	12	38	16	2.60	<0.01	6	1.15	537	<1	24	461	6	0.32	<5	<5	<10	241	2279	<2	92	18	13	43
190023	1361451	0.115	2	4.41	67	401	<2	12	0.30	<4	6	25	13	1.51	<0.01	7	0.44	167	<1	44	382	47	1.55	<5	9	<10	88	1237	<2	32	<10	5	101
190024	1361452	0.340	2	3.87	45	386	2	17	0.43	<4	6	25	25	1.31	<0.01	6	0.58	188	<1	41	381	94	1.30	<5	<5	<10	103	1021	<2	32	<10	5	97
190025	1361453	0.298	4	4.24	37	376	<2	16	0.56	<4	5	28	27	1.34	<0.01	6	0.71	342	<1	51	363	229	1.27	<5	<5	<10	99	916	2	29	<10	6	350
190026	1361454	0.154	<1	3.36	47	398	2	15	<0.01	<4	6	27	16	1.47	<0.01	1	0.33	<100	<1	51	345	61	1.56	<5	8	<10	67	959	<2	29	<10	5	190
190027	1361455	0.137	<1	3.84	43	415	2	3	0.77	<4	6	33	15	1.47	<0.01	6	0.77	420	<1	60	370	58	1.17	<5	<5	<10	86	1062	<2	31	<10	6	75
190028	1361456	0.127	<1	3.55	42	396	<2	12	0.73	<4	6	23	14	1.32	<0.01	5	0.76	399	<1	40	364	56	1.06	<5	<5	11	83	1013	<2	29	<10	5	80
190029	1361457	0.184	<1	3.46	43	383	<2	6	0.54	<4	6	25	14	1.22	<0.01	4	0.65	325	<1	44	382	51	1.03	<5	7	<10	81	1098	3	30	<10	5	121
190030	1361458	0.996	3	3.46	49	362	<2	12	<0.01	<4	6	20	34	1.39	<0.01	3	0.39	<100	<1	35	356	129	1.53	<5	5	<10	64	1132	<2	30	<10	5	438
190031D	1361458	1.083	3	3.62	47	350	<2	25	<0.01	<4	6	19	32	1.34	<0.01	4	0.40	<100	<1	35	352	120	1.45	<5	<5	<10	65	1104	<2	29	<10	5	415
190032	1361459	0.280	<1	3.31	43	390	<2	9	0.02	<4	7	18	16	1.41	<0.01	3	0.41	111	<1	35	369	51	1.49	<5	<5	<10	62	1265	<2	29	<10	5	153
190033	1361460	4.973	55	1.32	37	380	<2	24	0.89	16	11	23	39	2.46	<0.01	2	0.71	388	<1	19	406	456	0.49	50	8	192	190	1503	<2	72	42	10	1475
190034	1361461	0.311	<1	3.01	47	386	<2	11	0.24	<4	5	14	14	0.92	<0.01	4	0.45	140	<1	28	327	31	0.89	<5	<5	<10	68	1244	<2	26	<10	5	76

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 7, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/04/2012
 Date Completed:
 Job #: 201242542
 Reference: TL 12 276
 Sample #: 79

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
190035	1361462	0.092	<1	4.85	25	509	<2	17	1.53	<4	7	21	5	1.41	<0.01	11	1.06	441	<1	38	412	33	0.80	<5	7	<10	93	1649	<2	32	<10	6	69
190036	1361463	0.038	<1	4.24	35	465	2	17	1.64	<4	7	20	7	1.43	<0.01	10	1.14	542	<1	36	392	34	0.68	<5	<5	<10	89	1649	3	31	<10	6	85
190037	1361464	0.615	2	4.25	87	358	<2	22	0.17	<4	14	91	67	2.25	<0.01	10	0.49	168	<1	67	390	124	2.32	<5	<5	<10	59	1783	<2	54	<10	10	429
190038	1361465	0.200	<1	4.60	47	358	2	18	1.35	<4	11	78	37	1.95	<0.01	12	1.09	577	<1	84	430	55	1.10	<5	8	<10	96	1655	<2	48	<10	9	141
190039	1361466	0.257	2	3.46	62	325	2	29	0.55	<4	12	80	45	1.92	<0.01	9	0.65	274	<1	62	378	197	1.79	<5	<5	<10	70	1652	<2	50	<10	9	747
190040	1361467	0.036	1	4.44	32	364	<2	14	1.77	<4	8	34	12	1.52	<0.01	11	1.10	475	<1	43	389	196	0.89	<5	<5	<10	101	1557	<2	37	<10	7	99

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 14, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/12/2012
 Date Completed: 08/01/2012
 Job #: 201242652
 Reference: TL 12 277
 Sample #: 311

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
198558	1408777	<0.005	1	7.40	<2	78	5	15	6.76	10	56	472	63	7.67	0.39	22	3.44	1795	20	242	240	<1	0.52	<5	10	<10	87	3172	15	233	<10	23	91
198559	1408778	<0.005	<1	6.37	<2	85	<2	7	6.95	8	63	502	111	9.66	0.38	16	3.30	2388	19	252	245	4	0.47	<5	5	<10	75	3232	9	239	<10	19	79
198560	1408779	<0.005	<1	5.35	<2	47	<2	4	7.77	9	62	472	89	10.00	0.37	11	3.67	2780	20	244	210	2	0.37	<5	7	<10	83	3042	6	229	<10	18	83
198561	1408780	<0.005	1	4.84	<2	441	<2	12	2.63	<4	19	55	38	3.49	0.37	12	1.45	694	7	124	625	6	0.31	<5	<5	<10	307	2783	<2	125	20	17	57
198562	1408781	<0.005	<1	5.91	<2	33	<2	12	6.48	5	54	414	108	6.11	0.41	11	3.27	1507	11	219	247	2	0.36	<5	5	<10	93	2952	6	257	<10	19	71
198563	1408782	<0.005	<1	6.03	<2	13	<2	3	6.53	5	52	356	94	5.86	0.43	9	3.64	1262	11	155	250	3	0.35	<5	<5	<10	116	2922	12	253	<10	19	68
198564	1408783	<0.005	<1	5.55	<2	11	<2	<1	6.63	5	53	402	103	7.16	0.50	15	4.72	1490	12	203	230	<1	0.32	<5	9	<10	118	2644	12	231	<10	18	74
198565	1408784	0.006	<1	4.03	<2	<1	<2	<1	6.96	6	64	650	203	7.70	0.42	16	5.66	1600	8	297	260	<1	0.32	5	6	<10	50	2336	4	189	<10	15	69
198566	1408785	<0.005	1	5.02	<2	<1	<2	3	6.85	7	80	949	89	8.11	0.45	12	4.96	1570	12	403	203	2	0.30	<5	<5	<10	80	2536	7	223	<10	18	78
198567	1408786	<0.005	<1	4.61	<2	<1	<2	7	6.64	6	75	923	80	7.86	0.44	10	4.78	1532	13	410	209	2	0.27	<5	5	<10	75	2456	17	216	<10	17	76
198568D	1408786	<0.005	3	4.79	<2	<1	<2	<1	6.68	6	76	925	80	7.90	0.52	11	4.81	1547	13	399	203	2	0.29	<5	7	<10	77	2628	7	216	<10	17	74
198569	1408787	0.009	<1	4.50	<2	<1	<2	<1	6.88	6	72	866	92	7.93	0.66	11	5.32	1584	13	383	209	6	0.30	<5	<5	<10	66	2530	8	205	<10	16	70
198570	1408788	<0.005	1	4.32	<2	<1	<2	6	6.26	7	70	821	70	8.19	0.42	17	6.14	1693	6	353	207	2	0.26	<5	6	<10	39	2375	4	195	<10	15	70
198571	1408789	<0.005	<1	4.99	<2	<1	<2	1	6.20	7	72	846	103	8.23	0.40	23	6.78	1595	6	355	234	<1	0.30	<5	<5	<10	43	2239	11	202	<10	16	78
198572	1408790	<0.005	<1	4.53	<2	4	<2	<1	6.09	7	67	776	97	7.87	0.40	18	6.31	1590	7	344	213	2	0.29	<5	<5	<10	65	2191	13	191	<10	15	69
198573	1408791	<0.005	2	4.82	<2	4	<2	5	6.31	6	67	689	93	7.70	0.51	16	5.84	1565	5	325	217	5	0.31	<5	<5	<10	68	2185	5	193	<10	16	68
198574	1408792	<0.005	2	4.98	<2	18	<2	3	6.85	6	63	667	75	7.68	0.36	20	4.88	1563	11	277	206	3	0.32	<5	<5	<10	87	2562	5	211	<10	16	68
198575	1408793	<0.005	3	5.35	<2	17	<2	6	7.53	6	65	646	143	7.38	0.40	12	3.98	1585	15	294	224	1	0.38	<5	<5	<10	88	2951	7	230	<10	17	66
198576	1408794	<0.005	<1	4.66	<2	11	<2	<1	6.34	7	68	697	97	7.83	0.44	13	5.11	1527	12	325	219	3	0.32	<5	13	<10	93	2497	7	215	<10	16	73
198577	1408795	<0.005	2	4.32	<2	13	<2	10	6.00	6	63	653	97	7.51	0.27	12	4.96	1437	12	284	216	<1	0.33	<5	10	<10	95	2325	11	206	<10	16	74

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 14, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/12/2012
 Date Completed: 08/01/2012
 Job #: 201242652
 Reference: TL 12 277
 Sample #: 311

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
198578	1408796	<0.005	1	4.68	<2	16	<2	<1	6.19	6	68	685	82	7.76	0.56	14	5.14	1522	13	314	212	<1	0.29	<5	<5	<10	95	2530	<2	210	<10	16	78
198579D	1408796	<0.005	2	4.63	<2	16	<2	7	6.16	6	67	683	80	7.73	0.58	14	5.10	1519	11	313	208	<1	0.28	<5	<5	<10	95	2573	2	209	<10	16	77
198580	1408797	<0.005	<1	5.33	<2	23	<2	<1	6.39	6	63	650	79	8.05	0.42	14	4.45	1682	16	297	227	3	0.29	<5	<5	<10	93	2625	14	216	<10	17	77
198581	1408798	<0.005	2	5.61	<2	31	<2	<1	6.86	7	74	596	143	7.64	0.47	11	3.37	1864	14	307	233	1	0.43	5	<5	<10	98	2894	11	236	<10	18	89
198582	1408799	<0.005	2	6.14	<2	23	<2	5	6.79	6	52	389	130	7.47	0.34	14	4.43	1490	11	216	241	4	0.41	<5	<5	<10	106	3194	8	232	<10	18	74
198583	1408800	4.990	73	4.16	32	501	<2	4	1.54	23	16	36	69	3.40	0.22	11	0.96	528	11	123	565	599	0.69	55	<5	225	261	1987	<2	101	55	15	1974
198584	1408801	<0.005	2	5.81	<2	40	<2	2	7.08	6	50	311	84	7.72	0.31	14	4.26	1451	12	170	306	6	0.34	<5	5	<10	103	3188	15	247	<10	19	93
198585	1408802	<0.005	<1	5.28	<2	20	<2	<1	5.86	7	52	322	150	7.79	0.44	16	4.48	1338	10	173	248	3	0.51	<5	<5	<10	80	2908	6	246	<10	19	88
198586	1408803	<0.005	2	5.79	<2	28	<2	<1	6.14	6	50	324	98	7.61	0.47	16	4.51	1379	14	161	246	<1	0.35	<5	<5	<10	91	2964	11	254	<10	19	66
198587	1408804	0.012	<1	5.22	<2	37	<2	2	5.67	6	46	274	103	7.54	0.48	14	4.38	1272	12	150	242	3	0.29	6	<5	<10	89	2964	12	253	<10	19	59
198588	1408805	<0.005	1	4.45	<2	37	<2	<1	5.06	6	42	242	101	7.06	0.49	13	4.18	1153	10	104	273	<1	0.27	<5	<5	<10	80	2718	4	233	<10	18	62
198589	1408806	<0.005	<1	4.76	<2	39	<2	<1	5.16	6	42	250	73	7.07	0.49	15	4.22	1166	13	159	252	3	0.28	6	<5	<10	84	2811	7	232	<10	18	59
198590D	1408806	<0.005	1	4.68	<2	38	<2	3	5.08	6	42	248	73	7.01	0.42	14	4.18	1159	14	158	245	3	0.28	<5	<5	<10	82	2819	4	228	<10	18	58
198591	1408807	<0.005	1	4.83	<2	59	<2	5	5.21	6	47	259	129	7.27	0.50	14	4.38	1243	13	144	243	<1	0.28	<5	9	<10	85	2720	2	247	<10	18	72
198592	1408808	<0.005	<1	5.41	<2	72	<2	3	5.15	6	44	264	56	7.43	0.39	21	4.66	1394	11	141	231	1	0.29	<5	5	<10	89	2978	<2	250	<10	19	68
198593	1408809	<0.005	<1	5.39	<2	115	<2	<1	4.92	6	45	256	54	7.59	0.42	21	4.83	1464	11	151	251	2	0.29	<5	8	<10	87	2860	9	257	<10	20	68
198594	1408810	0.013	1	6.20	<2	186	<2	10	4.79	6	46	255	80	7.41	0.30	23	4.80	1645	12	110	259	6	0.35	<5	<5	<10	89	3004	7	249	<10	20	64
198595	1408811	<0.005	<1	5.26	<2	298	<2	<1	3.95	6	44	260	59	7.39	0.37	27	4.76	1634	11	148	241	3	0.28	<5	<5	<10	78	2538	8	233	<10	19	63
198596	1408812	<0.005	1	5.08	<2	118	<2	6	5.11	6	45	247	92	7.24	0.40	17	4.35	1383	12	188	241	3	0.28	<5	<5	<10	84	2668	4	240	<10	19	58
198597	1408813	<0.005	<1	5.38	<2	148	<2	<1	5.22	6	44	250	72	7.50	0.44	18	4.55	1496	11	170	251	4	0.27	<5	8	<10	86	2923	5	248	<10	19	64

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 14, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/12/2012
 Date Completed: 08/01/2012
 Job #: 201242652
 Reference: TL 12 277
 Sample #: 311

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
198598	1408814	<0.005	2	5.50	<2	39	<2	<1	5.45	6	48	289	111	7.85	0.47	19	4.69	1244	12	186	253	<1	0.33	<5	<5	<10	84	2735	12	257	<10	19	81
198599	1408815	<0.005	2	4.98	<2	10	<2	6	6.43	6	48	388	109	7.45	0.47	13	4.81	1300	12	243	240	<1	0.32	6	7	<10	75	2567	12	215	<10	17	70
198600	1408816	<0.005	1	5.81	<2	35	<2	9	6.84	6	53	394	127	7.63	0.59	14	4.29	1519	11	212	245	8	0.37	<5	<5	<10	100	3093	10	244	<10	19	80
198601D	1408816	<0.005	<1	5.67	<2	33	<2	5	6.75	6	52	391	130	7.59	0.47	14	4.26	1508	15	229	252	<1	0.38	<5	13	<10	97	2993	12	241	<10	18	78
198602	1408817	<0.005	<1	6.44	<2	39	<2	<1	7.68	7	59	431	190	8.49	0.52	12	3.76	1873	19	239	242	3	0.76	<5	<5	<10	87	3239	<2	253	<10	18	101
198603	1408818	<0.005	<1	4.89	<2	37	<2	2	7.61	7	58	375	293	8.76	0.40	15	2.69	2447	18	286	560	3	1.20	<5	9	<10	61	2492	8	200	<10	17	69
198604	1408819	<0.005	2	5.33	<2	59	<2	5	8.30	7	55	441	86	8.86	0.40	20	2.58	2470	17	253	238	3	0.42	<5	<5	<10	87	2997	4	229	<10	18	61
198605	1408820	<0.005	2	4.98	<2	432	<2	<1	2.64	<4	18	56	42	3.45	0.39	13	1.43	697	7	137	603	1	0.33	<5	<5	<10	302	2783	<2	123	20	17	53
198606	1408821	<0.005	1	6.14	<2	112	<2	13	7.59	7	53	517	97	7.93	0.32	21	3.54	1940	17	212	231	<1	0.35	<5	<5	<10	108	3265	10	240	<10	19	128
198607	1408822	<0.005	2	6.80	<2	46	<2	6	6.41	7	63	547	100	8.74	0.36	19	3.80	1970	18	270	233	<1	0.42	<5	11	<10	114	3506	6	253	<10	20	89
198608	1408823	<0.005	<1	6.38	<2	92	<2	1	6.51	7	55	512	82	8.51	0.41	13	3.53	1881	19	252	229	2	0.34	5	<5	<10	122	3097	15	236	<10	19	78
198609	1408824	<0.005	1	6.32	<2	73	<2	<1	6.91	6	59	531	121	8.10	0.40	11	3.38	1888	17	237	236	2	0.40	<5	10	<10	102	3193	13	247	<10	19	80
198610	1408825	<0.005	<1	5.70	<2	126	<2	5	7.32	9	60	499	235	10.13	0.45	16	3.92	2410	20	201	216	2	0.81	<5	<5	<10	77	3129	<2	237	<10	19	86
198611	1408826	<0.005	1	5.94	<2	115	<2	3	7.53	8	54	489	119	9.94	0.43	16	3.87	2432	21	218	217	<1	0.69	<5	7	<10	76	3076	7	235	<10	19	83
198612D	1408826	<0.005	<1	5.32	<2	109	<2	9	7.33	8	51	478	115	9.73	0.45	14	3.78	2379	20	217	209	2	0.64	<5	12	<10	70	2844	10	227	<10	19	82
198613	1408827	0.006	<1	6.12	<2	28	<2	4	7.82	7	56	536	195	8.10	0.45	13	3.00	1946	18	242	238	2	0.52	<5	<5	<10	126	3316	5	252	<10	19	94
198614	1408828	0.007	<1	5.63	<2	30	<2	7	6.57	6	60	533	104	7.43	0.44	10	3.17	1701	15	263	221	<1	0.36	<5	<5	<10	108	2960	6	236	<10	17	74
198615	1408829	0.009	<1	5.28	<2	65	<2	5	5.92	6	54	482	65	7.59	0.29	12	3.27	1685	15	231	210	2	0.29	<5	<5	<10	90	2745	11	219	<10	18	70
198616	1408830	0.009	<1	6.11	<2	73	<2	5	6.47	7	55	512	89	8.21	0.41	14	3.63	1769	18	233	222	5	0.32	<5	6	<10	106	2894	4	232	<10	19	82
198617	1408831	0.009	2	6.20	<2	38	<2	5	6.60	7	50	467	56	7.92	0.44	13	3.47	1730	16	174	210	<1	0.34	<5	<5	<10	119	2832	6	225	<10	18	75

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 14, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/12/2012
 Date Completed: 08/01/2012
 Job #: 201242652
 Reference: TL 12 277
 Sample #: 311

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
198618	1408832	0.009	2	7.66	<2	106	<2	11	6.77	7	64	585	110	7.88	0.42	15	3.31	1855	19	272	254	5	0.40	<5	6	<10	130	3335	16	255	<10	20	80
198619	1408833	<0.005	2	6.27	<2	59	<2	<1	6.00	6	56	527	79	7.43	0.33	13	3.08	1685	18	215	248	6	0.34	<5	<5	<10	120	3109	7	225	<10	18	73
198620	1408834	0.007	3	6.75	<2	71	<2	4	5.79	6	58	551	104	7.33	0.28	14	2.95	1861	17	244	266	2	0.33	<5	<5	<10	118	3534	11	249	<10	19	77
198621	1408835	0.005	<1	6.33	<2	69	<2	3	5.64	6	56	512	140	7.59	0.31	13	3.14	1745	15	283	251	2	0.35	<5	10	<10	102	2964	15	235	<10	19	75
198622	1408836	0.005	1	6.29	<2	136	<2	<1	6.37	7	60	523	113	7.81	0.39	14	3.21	1774	17	248	234	5	0.41	8	<5	<10	118	3217	3	240	<10	19	77
198623R	1408836	0.009	<1	7.87	<2	147	<2	6	6.69	7	60	526	111	7.86	0.41	19	3.25	1812	22	200	246	6	0.53	<5	<5	<10	134	3592	18	246	<10	20	131
198624	1408837	0.009	1	5.55	<2	164	<2	6	6.74	6	63	566	100	7.30	0.25	9	3.07	1678	17	218	241	4	0.32	<5	<5	<10	107	3083	12	236	<10	19	93
198625	1408838	0.008	<1	5.36	<2	40	<2	10	6.92	6	61	532	77	7.81	0.26	14	3.32	1930	14	168	223	<1	0.33	<5	<5	<10	106	3225	3	238	<10	19	83
198626	1408839	0.011	<1	4.40	<2	36	<2	3	7.10	6	55	507	95	6.86	0.38	14	2.83	2204	15	199	202	<1	0.34	<5	7	<10	82	2960	4	231	<10	17	72
198627	1408840	1.842	2	3.54	3	403	<2	<1	2.32	<4	19	55	39	3.78	0.40	11	1.43	714	8	72	628	7	0.27	<5	5	<10	255	2532	<2	126	17	17	73
198628	1408841	0.008	<1	5.04	<2	34	<2	4	6.99	6	61	539	85	7.56	0.41	10	2.82	1846	16	208	227	2	0.32	<5	<5	<10	110	2994	13	237	<10	18	67
198629	1408842	0.009	2	5.27	<2	55	<2	5	7.50	7	59	521	68	8.49	0.48	9	3.13	2330	19	194	223	<1	0.33	<5	8	<10	102	3003	8	234	10	18	79
198630	1408843	0.007	2	4.46	<2	34	<2	6	7.24	6	59	505	98	6.85	0.44	6	2.58	1843	15	208	233	1	0.32	<5	<5	<10	108	2950	8	227	<10	18	67
198631	1408844	0.008	3	4.58	<2	30	<2	<1	6.19	5	59	515	90	6.57	0.48	2	2.64	1732	14	216	235	<1	0.31	<5	7	<10	97	2771	9	224	<10	17	72
198632	1408845	0.009	2	4.82	<2	25	<2	3	7.10	7	56	516	81	8.57	0.60	7	3.55	2147	18	185	233	2	0.30	6	<5	<10	99	3003	7	234	<10	19	91
198633	1408846	<0.005	<1	4.19	<2	19	<2	<1	6.61	7	55	502	92	8.71	0.51	7	3.56	2127	18	179	232	2	0.29	<5	6	<10	78	2645	<2	226	<10	18	80
198634D	1408846	<0.005	2	4.64	<2	22	<2	13	6.74	7	56	509	93	8.81	0.43	9	3.58	2164	17	185	238	<1	0.31	<5	<5	<10	84	2792	7	228	<10	19	75
198635	1408847	<0.005	1	4.59	<2	30	<2	6	7.12	6	56	494	101	7.19	0.38	2	2.86	1989	15	204	224	3	0.30	<5	<5	<10	111	3067	4	222	<10	18	72
198636	1408848	<0.005	<1	4.64	<2	18	<2	<1	7.41	6	52	483	74	6.92	0.31	10	2.77	1714	16	191	221	3	0.29	<5	6	<10	129	3085	3	215	<10	17	55
198637	1408849	<0.005	<1	4.24	<2	22	<2	1	6.75	6	57	489	70	6.81	0.22	6	2.72	1783	14	199	213	2	0.27	<5	<5	<10	107	3101	2	223	<10	17	68

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 14, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/12/2012
 Date Completed: 08/01/2012
 Job #: 201242652
 Reference: TL 12 277
 Sample #: 311

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
198638	1408850	<0.005	1	4.60	<2	43	<2	<1	6.56	7	56	494	60	7.96	0.26	7	3.33	1983	15	168	215	<1	0.32	<5	<5	<10	91	2896	16	218	<10	17	77
198639	1408851	0.005	<1	4.61	<2	40	<2	2	6.34	6	55	510	68	7.46	0.27	9	3.09	1849	16	172	215	5	0.26	<5	9	<10	105	2818	16	224	<10	17	79
198640	1408852	<0.005	<1	4.53	<2	32	<2	<1	6.60	7	58	517	76	8.21	0.30	10	3.35	1910	15	181	214	3	0.26	<5	<5	<10	84	2833	19	232	<10	18	82
198641	1408853	0.007	2	4.59	<2	30	<2	5	5.75	6	61	516	191	7.99	0.38	10	3.23	1928	14	204	215	<1	0.35	<5	<5	<10	86	2853	13	232	<10	17	81
198642	1408854	0.006	<1	4.69	<2	38	<2	<1	6.51	7	58	507	113	7.84	0.40	8	3.24	1951	18	188	220	4	0.29	<5	<5	<10	105	2805	7	235	<10	18	102
198643	1408855	0.006	<1	4.74	<2	33	<2	10	6.50	6	57	526	63	7.54	0.50	9	3.35	1684	14	166	221	<1	0.26	<5	<5	<10	122	2788	12	238	<10	18	76
198644	1408856	0.009	<1	4.73	<2	33	<2	11	7.44	6	58	520	103	7.37	0.41	8	2.77	2075	15	209	216	4	0.33	<5	9	<10	101	2659	7	232	<10	17	71
198645D	1408856	0.008	1	5.05	<2	37	<2	<1	7.51	6	59	512	103	7.35	0.57	9	2.75	2052	16	215	215	1	0.34	<5	<5	<10	107	2695	8	234	<10	17	71
198646	1408857	0.006	2	4.75	<2	50	<2	14	6.83	7	58	493	114	8.14	0.52	11	3.34	2041	17	174	217	<1	0.30	<5	<5	<10	113	2892	13	234	<10	18	90
198647	1408858	0.005	<1	4.99	<2	40	<2	8	6.83	8	60	527	97	9.18	0.47	17	3.52	2169	18	160	218	2	0.30	<5	<5	<10	112	3007	<2	245	<10	19	87
198648	1408859	0.011	2	5.25	<2	44	<2	6	6.94	7	61	498	71	8.98	0.38	12	3.45	2139	20	184	230	4	0.35	<5	6	<10	107	2897	4	231	<10	19	86
198649	1408860	<0.005	2	3.33	<2	363	<2	<1	2.37	<4	19	54	27	3.45	0.10	10	1.40	687	7	63	606	2	0.27	<5	<5	<10	258	2696	<2	119	15	17	54
198650	1408861	0.008	<1	4.55	<2	34	<2	4	5.77	6	54	493	66	7.83	0.20	13	3.49	1793	15	163	237	<1	0.31	<5	<5	<10	95	2958	2	223	<10	19	79
198651	1408862	0.013	<1	5.21	<2	51	3	3	7.17	8	55	510	93	7.44	0.33	15	3.01	1798	17	167	232	2	0.38	<5	<5	<10	115	3070	6	230	<10	20	82
198652	1408863	0.007	<1	4.52	<2	56	<2	7	7.16	5	53	441	97	6.30	0.44	7	2.02	1866	12	180	216	2	0.35	<5	5	<10	120	3034	4	204	<10	17	53
198653	1408864	0.006	2	4.34	<2	25	<2	4	8.03	8	55	483	109	9.39	0.48	15	3.37	2632	18	182	193	1	0.36	<5	<5	<10	63	2704	<2	220	<10	18	78
198654	1408865	0.006	<1	4.95	<2	41	<2	2	5.96	6	59	498	93	7.56	0.58	14	3.32	1983	14	201	262	<1	0.31	<5	<5	<10	74	2692	7	236	<10	18	76
198655	1408866	<0.005	<1	4.26	<2	31	<2	5	5.57	6	57	483	95	7.28	0.48	13	3.21	1900	15	199	223	1	0.29	<5	<5	<10	69	2542	7	226	<10	17	73
198656D	1408866	<0.005	3	4.97	<2	37	<2	<1	5.76	6	59	496	98	7.48	0.52	15	3.30	1958	13	203	227	3	0.32	<5	<5	<10	75	2731	2	234	<10	18	76
198657	1408867	<0.005	<1	4.95	<2	43	<2	18	6.95	6	52	427	79	6.66	0.52	8	2.52	1863	13	194	242	<1	0.32	<5	<5	<10	124	3179	7	233	<10	18	67

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 14, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/12/2012
 Date Completed: 08/01/2012
 Job #: 201242652
 Reference: TL 12 277
 Sample #: 311

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
198658	1408868	<0.005	<1	5.83	<2	34	<2	2	6.78	7	64	513	95	8.11	0.74	16	3.17	2290	18	217	245	1	0.38	<5	<5	<10	94	3370	6	254	<10	19	69
198659	1408869	0.007	2	6.14	<2	27	<2	2	7.00	8	61	519	105	9.87	0.44	17	3.71	2502	20	215	249	<1	0.37	<5	<5	<10	76	3050	13	236	<10	20	79
198660	1408870	0.006	<1	4.87	<2	16	<2	<1	6.45	7	55	478	100	8.93	0.34	9	3.51	2386	17	173	225	<1	0.35	<5	<5	<10	97	2925	10	226	<10	19	80
198661	1408871	<0.005	2	4.77	<2	37	<2	7	6.30	6	58	508	97	7.39	0.37	9	2.83	2310	15	191	227	<1	0.30	<5	<5	<10	125	3171	7	226	<10	18	72
198662	1408872	<0.005	<1	5.26	<2	41	<2	<1	7.03	7	56	524	56	8.89	0.39	21	3.57	2487	19	169	218	<1	0.28	<5	<5	<10	127	3124	<2	239	<10	19	82
198663	1408873	<0.005	<1	4.76	<2	33	<2	9	7.90	7	70	534	427	8.37	0.48	16	3.19	2157	18	192	234	1	0.50	<5	<5	<10	126	3444	8	241	<10	18	113
198664	1408874	<0.005	2	5.40	4	57	<2	10	7.27	7	61	506	145	8.24	0.44	9	3.06	2271	17	201	228	5	0.43	<5	6	<10	175	3415	11	240	<10	19	95
198665	1408875	<0.005	2	5.25	<2	48	<2	8	6.60	7	59	518	83	8.45	0.47	13	3.31	2218	17	188	237	8	0.32	<5	<5	<10	162	3400	6	242	<10	19	84
198666	1408876	0.007	2	4.57	<2	44	<2	<1	5.54	7	60	440	131	7.97	0.49	14	3.61	1977	17	180	247	<1	0.44	<5	<5	<10	102	3416	3	246	<10	18	79
198667D	1408876	0.006	2	3.92	<2	37	<2	10	5.37	7	59	440	133	7.94	0.48	13	3.59	1962	15	173	241	3	0.41	<5	<5	<10	92	3414	4	245	<10	18	77
198668	1408877	<0.005	<1	4.31	<2	40	<2	<1	5.29	6	52	297	137	7.35	0.44	15	3.73	1416	11	126	255	3	0.36	<5	6	<10	116	3841	12	254	<10	20	72
198669	1408878	<0.005	2	4.69	<2	30	<2	<1	5.83	6	46	248	127	7.88	0.55	13	4.10	1468	14	96	250	4	0.35	6	<5	<10	96	3448	<2	257	<10	20	81
198670	1408879	0.007	2	4.52	<2	25	<2	11	7.72	7	43	218	163	8.76	0.52	4	3.08	2302	18	98	249	2	0.53	<5	<5	<10	114	3286	8	228	<10	19	71
198671	1408880	0.243	1	<0.01	509	>5000	<2	3	0.94	<4	6	17	38	3.03	0.30	4	0.20	<100	17	57	<100	14	0.63	14	<5	<10	116	767	6	17	43	8	21
198672	1408881	0.007	1	5.19	<2	67	<2	4	6.41	6	47	249	102	7.73	0.44	9	3.32	1835	17	98	246	1	0.47	<5	5	<10	124	3327	16	235	<10	19	72
198673	1408882	0.007	<1	5.33	2	45	<2	16	5.74	5	42	238	69	6.11	0.39	18	3.19	1447	11	95	256	6	1.05	<5	6	<10	162	3737	6	245	<10	19	90
198674	1408883	0.006	1	4.88	<2	359	<2	3	1.92	4	25	51	114	4.09	0.22	16	0.79	362	12	120	256	5	2.71	<5	<5	<10	109	1294	<2	46	<10	8	224
198675	1408884	0.006	<1	4.92	<2	413	<2	4	2.40	<4	19	113	51	3.32	0.26	27	1.36	455	14	137	580	8	1.81	<5	<5	<10	126	2105	2	72	<10	14	163
198676	1408885	<0.005	2	4.63	<2	458	<2	<1	1.09	<4	17	53	48	3.07	0.34	21	0.90	273	13	110	359	13	1.88	5	7	<10	140	1646	<2	44	14	10	165
198677	1408886	0.006	1	4.24	<2	471	<2	<1	0.96	<4	18	60	47	3.20	0.37	20	0.89	266	13	128	341	6	1.93	<5	<5	<10	131	1640	<2	45	<10	10	147

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 14, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/12/2012
 Date Completed: 08/01/2012
 Job #: 201242652
 Reference: TL 12 277
 Sample #: 311

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
198678D	1408886	0.006	1	4.96	<2	480	<2	<1	1.01	<4	18	61	48	3.22	0.38	22	0.91	268	14	134	346	5	2.00	<5	<5	<10	141	1676	<2	46	<10	11	171
198679	1408887	0.006	<1	5.12	<2	369	2	4	1.24	<4	25	152	48	4.05	0.39	25	1.49	561	13	119	523	13	0.73	<5	5	<10	247	2697	3	97	<10	16	72
198680	1408888	0.007	<1	5.09	<2	522	<2	<1	0.98	<4	28	164	52	4.53	0.41	31	1.71	555	13	144	538	13	0.39	<5	<5	<10	210	2999	<2	118	<10	19	77
198681	1408889	0.009	<1	5.43	<2	518	2	3	0.92	4	28	163	53	4.75	0.49	32	1.80	593	13	137	555	16	0.42	6	6	<10	205	3137	<2	123	<10	20	76
198682	1408890	0.009	2	5.21	<2	444	<2	<1	1.10	<4	24	147	57	4.05	0.56	28	1.48	566	12	134	524	13	0.46	<5	<5	<10	247	2659	<2	95	<10	17	69
198683	1408891	0.011	<1	5.65	<2	551	<2	<1	0.95	4	27	155	48	4.30	0.40	32	1.64	514	13	110	535	11	0.48	<5	<5	<10	225	2962	<2	108	<10	18	76
198684	1408892	0.006	<1	4.56	<2	566	<2	<1	0.78	<4	26	158	55	4.21	0.29	30	1.60	545	12	129	517	12	0.45	<5	<5	<10	194	2895	<2	103	<10	17	74
198685	1408893	0.008	2	5.77	<2	665	2	<1	1.20	4	29	170	66	4.50	0.20	34	1.70	597	14	146	543	11	0.47	<5	<5	<10	250	3295	5	119	<10	18	77
198686	1408894	0.010	2	7.01	<2	676	2	<1	1.36	<4	22	132	54	3.64	0.30	31	1.44	497	11	134	541	14	0.52	<5	<5	<10	339	3070	<2	92	<10	17	70
198687	1408895	0.008	1	4.28	<2	773	<2	<1	0.80	<4	23	148	49	3.70	0.17	29	1.43	488	11	136	567	12	0.43	<5	5	<10	218	2656	<2	95	<10	16	70
198688	1408896	0.008	2	4.56	<2	689	<2	<1	0.83	<4	22	158	49	3.97	0.27	31	1.51	483	13	136	528	13	0.45	<5	<5	<10	250	2679	4	92	<10	16	74
198689R	1408896	0.008	2	2.36	<2	644	<2	<1	0.50	<4	23	151	49	3.93	0.31	26	1.47	486	10	128	510	14	0.32	<5	<5	<10	187	2558	<2	92	<10	15	114
198690	1408897	0.008	<1	5.30	<2	582	<2	<1	1.13	4	25	166	58	4.24	0.30	32	1.55	569	13	140	550	17	0.45	<5	<5	<10	280	3051	<2	106	<10	17	226
198691	1408898	0.011	1	5.11	<2	683	2	4	0.91	4	30	167	52	4.62	0.32	35	1.68	556	13	133	535	18	0.31	<5	<5	<10	230	3299	<2	126	<10	18	119
198692	1408899	0.007	1	4.70	<2	563	<2	<1	1.30	<4	24	158	49	4.07	0.24	29	1.43	571	12	124	539	16	0.34	<5	<5	<10	293	2922	<2	99	<10	16	90
198693	1408900	<0.005	2	2.82	<2	386	<2	<1	2.32	<4	17	53	29	3.42	0.20	7	1.36	676	6	75	611	1	0.20	5	<5	<10	264	2658	<2	120	17	16	65
198694	1408901	0.011	<1	4.38	<2	593	<2	<1	0.81	<4	26	155	50	4.26	0.15	32	1.56	544	11	124	561	9	0.36	<5	5	<10	208	2901	2	109	<10	17	81
198695	1408902	<0.005	1	3.51	<2	556	<2	<1	0.78	<4	25	150	53	4.05	0.61	31	1.49	497	10	126	531	12	0.40	<5	<5	<10	215	2512	4	96	<10	15	76
198696	1408903	<0.005	2	3.01	<2	555	<2	<1	0.74	<4	23	143	48	3.70	0.39	29	1.38	457	9	102	519	16	0.38	<5	<5	<10	229	2290	<2	87	<10	14	80
198697	1408904	0.006	<1	2.95	<2	580	<2	<1	0.81	<4	22	141	46	3.50	0.36	28	1.32	477	9	108	499	11	0.38	<5	<5	<10	243	2179	4	81	<10	14	82

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 14, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/12/2012
 Date Completed: 08/01/2012
 Job #: 201242652
 Reference: TL 12 277
 Sample #: 311

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
198698	1408905	<0.005	<1	2.84	<2	545	<2	<1	0.71	<4	19	132	35	3.05	0.50	25	1.17	407	11	104	509	11	0.34	<5	<5	<10	223	1948	<2	70	11	12	61
198699	1408906	<0.005	2	3.21	<2	509	<2	2	0.84	<4	18	125	40	3.05	0.42	25	1.17	401	9	100	457	13	0.37	<5	<5	<10	254	1941	<2	69	<10	12	125
198700D	1408906	0.007	<1	3.08	<2	513	<2	<1	0.84	<4	17	128	40	3.11	0.41	25	1.19	408	9	112	463	13	0.36	<5	<5	<10	256	1946	<2	70	<10	12	67
198701	1408907	0.005	2	3.37	<2	884	<2	<1	0.66	<4	26	161	49	4.15	0.38	34	1.58	545	11	143	522	13	0.30	<5	7	<10	218	2929	<2	110	<10	15	89
198702	1408908	<0.005	9	3.25	<2	750	<2	<1	0.80	<4	23	153	48	3.84	0.20	30	1.42	495	12	142	512	12	0.33	<5	6	<10	259	2669	<2	93	<10	14	76
198703	1408909	<0.005	1	3.25	<2	765	2	4	0.59	<4	25	153	49	4.03	0.09	34	1.52	475	10	128	516	12	0.33	<5	<5	<10	226	2726	<2	98	<10	14	81
198704	1408910	0.005	<1	4.41	<2	667	2	<1	0.92	4	28	188	49	4.64	0.25	39	1.91	565	12	132	658	13	0.34	<5	<5	<10	241	3101	<2	118	<10	16	84
198705	1408911	<0.005	1	4.14	<2	689	<2	<1	0.60	4	28	168	47	4.61	0.30	38	1.67	525	12	125	547	10	0.31	<5	<5	<10	189	2991	4	119	<10	16	78
198706	1408912	0.006	1	3.84	<2	482	2	<1	0.83	<4	27	153	37	4.13	0.27	31	1.50	583	10	106	538	11	0.29	<5	<5	<10	210	2760	3	104	<10	15	90
198707	1408913	0.005	<1	4.61	<2	809	<2	8	0.38	4	31	173	56	4.80	0.24	43	1.80	442	16	130	547	10	0.39	<5	<5	<10	140	2907	5	126	<10	15	90
198708	1408914	0.008	1	3.95	<2	726	<2	<1	0.43	<4	27	152	45	4.44	0.38	41	1.67	422	11	104	549	7	0.35	<5	<5	<10	149	2623	<2	109	<10	14	91
198709	1408915	0.005	<1	2.91	<2	481	<2	<1	0.88	<4	23	142	49	3.68	1.34	29	1.34	531	10	101	523	14	0.33	<5	<5	<10	222	2123	<2	87	<10	13	69
198710	1408916	0.012	<1	4.29	<2	769	2	3	0.42	4	28	170	51	4.82	0.49	53	1.83	475	22	128	583	12	0.31	<5	<5	<10	174	2702	<2	119	<10	14	91
198711D	1408916	0.011	<1	4.53	<2	739	3	<1	0.49	4	27	165	50	4.68	0.51	52	1.78	458	23	127	580	9	0.32	<5	<5	<10	190	2621	<2	114	<10	14	89
198712	1408917	0.007	<1	5.09	<2	790	2	3	0.52	4	30	166	50	5.01	0.44	51	1.94	468	14	116	556	11	0.39	<5	10	<10	192	2861	4	121	<10	13	92
198713	1408918	0.008	<1	5.89	<2	959	<2	2	0.58	4	30	180	47	4.83	0.35	47	1.85	474	14	122	566	11	0.40	<5	8	<10	214	3330	4	131	<10	13	90
198714	1408919	0.009	<1	3.97	<2	667	<2	<1	0.75	4	25	156	45	4.20	0.21	34	1.56	508	11	104	536	12	0.30	<5	6	<10	236	2880	<2	104	<10	12	79
198715	1408920	5.372	69	2.47	32	478	<2	1	1.31	22	17	33	54	3.42	0.38	6	0.85	513	9	36	551	608	0.55	52	<5	232	244	1889	<2	99	52	13	1949
198716	1408921	0.005	1	4.85	<2	571	<2	<1	1.00	<4	25	155	44	4.17	0.32	34	1.51	546	11	102	540	21	0.35	<5	<5	<10	264	2954	<2	107	<10	14	90
198717	1408922	0.010	2	4.72	<2	515	2	<1	1.16	<4	25	157	46	4.04	0.44	30	1.43	553	12	106	500	21	0.41	<5	<5	<10	297	2856	2	105	<10	14	69

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 14, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/12/2012
 Date Completed: 08/01/2012
 Job #: 201242652
 Reference: TL 12 277
 Sample #: 311

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
198718	1408923	0.010	<1	4.65	<2	564	<2	<1	1.03	<4	25	153	48	4.18	<0.01	33	1.51	535	10	97	544	13	0.36	<5	<5	<10	255	2827	<2	110	<10	14	74
198719	1408924	0.009	1	4.11	<2	585	<2	<1	0.76	4	26	163	48	4.34	0.29	34	1.59	512	12	109	531	14	0.36	<5	6	<10	193	2705	2	112	<10	12	76
198720	1408925	0.011	1	4.91	<2	658	2	<1	1.02	<4	25	161	49	4.31	0.29	41	1.65	498	10	93	611	12	0.43	<5	<5	<10	283	2680	4	107	<10	13	84
198721	1408926	0.008	<1	3.33	<2	583	<2	2	0.70	<4	25	155	47	4.17	0.32	37	1.57	470	10	95	551	15	0.38	<5	<5	<10	222	2386	<2	100	<10	12	79
198722D	1408926	0.010	1	4.13	<2	591	<2	<1	0.86	4	27	157	48	4.26	0.35	40	1.62	474	9	93	563	11	0.42	<5	<5	<10	252	2471	<2	103	<10	13	83
198723	1408927	0.010	1	3.36	<2	580	<2	<1	0.84	<4	22	149	44	3.72	0.36	33	1.39	435	11	97	508	12	0.37	<5	<5	<10	269	2202	<2	85	<10	12	71
198724	1408928	0.010	<1	3.29	<2	473	<2	5	0.89	<4	22	143	41	3.52	0.35	32	1.31	440	10	94	459	12	0.37	<5	<5	<10	250	2048	<2	85	<10	12	66
198725	1408929	0.011	<1	3.04	<2	535	<2	<1	0.80	<4	22	170	49	3.88	0.28	33	1.39	503	13	149	510	11	0.30	<5	<5	<10	269	2516	<2	87	<10	12	75
198726	1408930	0.012	<1	3.56	<2	688	<2	<1	0.58	<4	26	158	49	4.26	0.30	38	1.57	480	11	136	530	12	0.29	<5	7	<10	203	2763	6	106	<10	11	78
198727	1408931	0.010	2	4.39	<2	484	2	4	0.94	<4	28	168	50	4.42	0.27	39	1.57	574	12	139	545	13	0.32	<5	<5	<10	206	2957	2	111	<10	13	81
198728	1408932	0.010	2	3.71	<2	486	<2	<1	0.76	<4	23	159	44	3.93	0.21	36	1.39	489	12	132	500	11	0.29	<5	<5	<10	189	2678	<2	102	<10	12	73
198729	1408933	0.006	<1	3.50	<2	619	<2	<1	0.66	<4	25	159	44	4.12	0.53	42	1.54	476	12	125	534	12	0.30	5	9	<10	214	2331	<2	104	<10	14	77
198730	1408934	0.006	<1	3.21	<2	611	<2	<1	0.90	<4	21	157	45	3.68	0.26	40	1.34	492	11	121	502	12	0.33	<5	9	<10	281	2428	3	86	<10	11	71
198731	1408935	0.014	<1	3.55	<2	570	2	<1	0.62	<4	25	174	49	4.21	0.20	48	1.52	515	16	148	530	10	0.39	<5	<5	<10	183	2311	<2	100	<10	13	75
198732	1408936	0.006	<1	3.78	<2	533	2	<1	0.83	<4	24	153	46	3.71	0.23	48	1.36	443	12	134	505	10	0.46	<5	<5	<10	255	2246	7	89	<10	11	69
198733D	1408936	0.008	<1	3.16	<2	528	2	<1	0.69	<4	22	157	47	3.82	0.23	48	1.39	448	13	140	510	13	0.45	<5	<5	<10	224	2212	<2	89	<10	11	72
198734	1408937	0.008	<1	3.67	<2	562	<2	<1	0.88	<4	22	150	47	3.60	0.31	41	1.37	443	11	121	498	14	0.40	<5	<5	<10	259	2237	<2	83	<10	11	74
198735	1408938	0.008	1	4.89	<2	551	<2	<1	0.97	<4	24	157	45	4.13	0.27	48	1.53	491	14	130	531	11	0.40	<5	<5	<10	230	2441	<2	103	<10	14	73
198736	1408939	0.020	1	3.97	<2	530	<2	<1	0.80	<4	23	160	50	4.09	0.35	44	1.49	444	13	137	508	9	0.38	<5	<5	<10	229	2267	<2	97	<10	13	72
198737	1408940	<0.005	2	2.94	<2	374	<2	<1	2.29	<4	17	52	27	3.39	0.21	8	1.35	676	5	67	601	<1	0.21	<5	<5	<10	262	2774	<2	118	15	16	53

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 14, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/12/2012
 Date Completed: 08/01/2012
 Job #: 201242652
 Reference: TL 12 277
 Sample #: 311

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
198738	1408941	0.009	1	3.57	<2	606	<2	3	0.81	<4	23	149	47	3.74	0.23	37	1.43	466	11	125	508	13	0.35	<5	<5	<10	266	2573	<2	87	<10	12	71
198739	1408942	0.008	<1	4.01	<2	707	<2	<1	0.99	<4	22	152	46	3.66	0.31	37	1.40	464	11	121	498	15	0.35	<5	7	<10	317	2625	8	88	<10	12	73
198740	1408943	0.009	1	3.91	<2	626	<2	<1	0.99	<4	24	167	48	4.05	0.21	35	1.44	488	14	151	512	10	0.34	<5	5	<10	268	2773	<2	100	<10	13	74
198741	1408944	0.007	<1	4.42	<2	617	<2	<1	0.98	<4	25	173	52	4.08	0.20	36	1.48	511	15	153	534	20	0.36	<5	<5	<10	296	2823	<2	100	<10	14	82
198742	1408945	0.005	<1	4.23	<2	609	<2	<1	1.17	<4	21	146	43	3.40	0.33	31	1.28	478	10	123	489	17	0.35	<5	<5	<10	274	2396	<2	90	<10	14	84
198743	1408946	0.007	<1	4.36	<2	589	<2	<1	1.14	<4	22	155	41	3.45	0.36	32	1.32	471	12	128	496	13	0.38	<5	<5	<10	265	2305	<2	89	<10	14	69
198744D	1408946	0.007	<1	4.20	<2	573	2	<1	1.13	<4	20	150	40	3.41	0.33	31	1.30	462	11	122	475	16	0.37	<5	8	<10	265	2265	<2	88	<10	14	68
198745	1408947	<0.005	1	2.74	<2	483	3	<1	0.72	4	21	142	46	3.43	0.38	30	1.28	387	11	118	503	11	0.33	<5	6	<10	213	2090	<2	81	<10	14	78
198746	1408948	0.005	1	3.16	<2	430	<2	<1	0.85	<4	19	137	42	3.39	0.36	28	1.28	396	9	116	515	11	0.35	<5	<5	<10	236	1995	<2	77	<10	11	62
198747	1408949	0.009	<1	3.83	<2	563	<2	<1	0.81	<4	24	164	47	4.01	0.32	34	1.45	451	14	145	501	12	0.38	<5	<5	<10	244	2291	<2	94	<10	12	74
198748	1408950	0.009	1	4.79	<2	452	<2	<1	1.32	<4	20	149	49	3.48	0.30	31	1.29	494	11	121	507	16	0.47	<5	8	<10	302	2152	3	81	<10	13	67
198749	1408951	0.006	1	4.31	<2	553	<2	<1	1.18	<4	21	163	46	3.53	0.13	29	1.32	494	14	136	556	13	0.40	<5	<5	<10	317	2473	<2	83	<10	12	66
198750	1408952	0.006	<1	4.34	<2	641	<2	1	0.95	<4	25	160	48	3.84	0.24	32	1.43	453	12	129	502	11	0.34	<5	<5	<10	293	2787	5	95	<10	12	70
198751	1408953	<0.005	<1	4.36	<2	588	2	<1	0.95	<4	24	155	51	3.85	0.27	29	1.40	513	12	124	514	13	0.34	<5	7	<10	299	2785	<2	99	<10	13	71
198752	1408954	0.006	<1	4.88	<2	603	2	3	1.15	<4	24	154	54	4.01	0.20	33	1.46	514	11	116	549	13	0.38	<5	5	<10	310	2832	<2	98	<10	14	75
198753	1408955	0.006	<1	4.85	<2	522	<2	<1	1.61	<4	21	181	50	3.89	0.20	28	1.26	646	17	161	542	20	0.43	<5	<5	<10	353	2557	<2	89	<10	14	73
198754	1408956	0.006	<1	8.08	3	660	2	<1	1.42	4	28	180	47	4.39	0.34	47	1.66	529	16	146	532	14	0.56	<5	<5	<10	307	3321	7	120	<10	15	113
198755R	1408956	0.006	1	8.56	<2	587	2	<1	1.67	<4	25	161	40	4.07	0.27	45	1.58	530	14	124	545	18	0.60	<5	<5	<10	338	3218	6	113	<10	15	91
198756	1408957	0.008	2	8.09	<2	535	2	<1	2.37	<4	23	163	49	3.56	0.45	38	1.29	665	15	127	563	16	0.69	<5	6	<10	363	2761	<2	87	<10	17	89
198757	1408958	0.006	<1	7.53	<2	659	2	2	1.59	<4	26	185	51	4.07	0.21	41	1.50	570	19	159	527	13	0.55	<5	<5	<10	292	2979	4	110	<10	16	88

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 14, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/12/2012
 Date Completed: 08/01/2012
 Job #: 201242652
 Reference: TL 12 277
 Sample #: 311

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
198758	1408959	0.007	1	8.56	<2	903	2	5	0.79	4	31	194	39	5.14	0.30	55	2.01	555	19	149	520	14	0.49	<5	8	<10	211	3613	5	153	<10	18	101
198759	1408960	1.743	2	7.00	<2	472	<2	<1	2.58	<4	19	55	36	3.69	0.36	21	1.51	702	10	62	626	3	0.49	<5	5	<10	304	2950	6	125	23	19	80
198760	1408961	0.018	2	8.77	<2	483	2	6	3.10	<4	25	196	60	4.11	0.44	38	1.52	727	20	157	470	15	0.79	<5	<5	<10	326	2920	<2	111	21	20	86
198761	1408962	0.008	<1	7.60	<2	517	2	2	1.78	4	22	192	61	3.92	0.36	38	1.33	624	20	153	554	19	0.71	<5	5	<10	339	2772	7	90	<10	16	78
198762	1408963	0.005	2	8.01	<2	564	2	7	1.52	<4	23	207	57	4.00	0.45	40	1.38	536	28	205	517	15	0.68	6	12	<10	345	2810	<2	92	<10	15	78
198763	1408964	0.006	<1	8.33	<2	557	2	<1	1.83	<4	24	201	49	4.18	0.39	42	1.45	625	24	170	568	15	0.68	<5	6	<10	373	3002	5	100	<10	17	80
198764	1408965	0.009	2	7.88	<2	495	<2	<1	2.11	<4	22	233	57	4.14	0.38	37	1.33	593	33	243	551	15	0.74	<5	14	<10	351	2777	2	92	<10	17	74
198765	1408966	0.009	1	7.65	<2	487	2	15	2.01	<4	21	180	49	3.77	0.32	37	1.35	649	16	123	493	16	0.72	<5	10	<10	345	2508	<2	88	<10	17	69
198766D	1408966	0.008	2	8.01	<2	486	<2	<1	2.08	<4	22	179	49	3.80	0.33	38	1.35	691	18	137	499	16	0.70	<5	<5	<10	354	2787	4	89	<10	17	73
198767	1408967	0.011	1	7.90	<2	657	2	<1	1.34	4	25	174	51	4.16	0.28	44	1.62	502	17	138	527	9	0.63	<5	<5	<10	343	3047	3	105	<10	18	77
198768	1408968	0.008	1	7.84	<2	548	2	4	1.59	<4	24	176	47	4.02	0.28	38	1.48	540	18	143	544	13	0.62	<5	5	<10	383	2985	2	97	<10	18	66
198769	1408969	0.007	2	8.31	<2	542	2	<1	1.78	<4	23	170	51	4.02	0.29	39	1.47	576	16	130	555	20	0.64	<5	<5	<10	352	2944	<2	99	<10	18	89
198770	1408970	0.008	1	9.01	<2	783	2	6	1.33	4	26	200	49	4.64	0.32	48	1.72	538	22	170	546	10	0.62	<5	<5	<10	282	3336	<2	123	<10	20	75
198771	1408971	0.008	1	8.94	<2	612	2	<1	1.45	<4	25	179	47	4.25	0.43	44	1.61	539	19	131	527	10	0.66	<5	<5	<10	291	3115	2	111	<10	19	71
198772	1408972	0.007	3	9.08	<2	596	2	<1	1.36	4	26	190	48	4.62	0.39	47	1.71	547	20	157	536	11	0.66	<5	<5	<10	284	3311	4	124	<10	20	74
198773	1408973	0.006	1	7.24	<2	521	2	<1	1.53	<4	24	173	47	3.90	0.37	38	1.47	529	17	131	512	10	0.58	<5	<5	<10	348	2837	<2	97	<10	18	54
198774	1408974	0.007	1	7.77	<2	541	2	<1	1.41	<4	24	178	45	4.06	0.54	40	1.57	526	20	147	526	22	0.61	<5	8	<10	351	2942	4	98	<10	19	85
198775	1408975	0.007	2	7.91	<2	546	2	<1	1.39	<4	23	163	53	3.98	0.51	41	1.57	516	15	131	533	16	0.60	<5	6	<10	317	3045	2	103	<10	19	67
198776	1408976	0.006	<1	8.14	<2	645	2	4	1.46	<4	24	158	47	4.07	0.71	43	1.61	520	16	131	568	15	0.59	<5	6	<10	357	3065	2	103	<10	18	80
198777D	1408976	0.008	1	8.24	<2	637	2	<1	1.45	<4	23	157	45	3.99	0.50	43	1.58	515	17	120	549	21	0.61	<5	<5	<10	353	3038	8	101	<10	18	78

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 14, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 07/12/2012
 Date Completed: 08/01/2012
 Job #: 201242652
 Reference: TL 12 277
 Sample #: 311

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
198778	1408977	0.008	3	8.34	<2	559	2	5	1.94	4	27	172	51	4.57	0.23	45	1.71	557	15	116	566	17	0.65	<5	<5	<10	427	3855	<2	115	10	19	70
198779	1408978	<0.005	1	7.79	<2	589	2	<1	1.94	4	28	169	44	4.85	0.27	46	1.83	651	17	120	626	11	0.59	<5	8	<10	316	4620	3	123	<10	20	117
198780	1408979	<0.005	1	7.96	<2	618	2	<1	1.46	4	26	169	49	4.09	0.24	42	1.54	521	13	122	532	16	0.60	<5	5	<10	301	3069	<2	107	<10	18	65
198781	1408980	<0.005	2	6.83	<2	444	<2	<1	2.72	<4	17	52	25	3.35	0.30	18	1.46	672	7	55	613	5	0.48	<5	5	<10	319	2962	<2	121	17	19	54
198782	1408981	<0.005	1	7.52	<2	678	<2	3	1.32	<4	23	175	48	3.95	0.44	40	1.54	514	16	132	548	17	0.57	<5	<5	<10	320	2955	<2	101	<10	17	70
198783	1408982	<0.005	<1	7.61	<2	638	2	<1	1.40	<4	23	171	44	3.85	0.63	39	1.48	506	18	145	528	14	0.58	<5	5	<10	323	2858	<2	96	<10	17	63
198784	1408983	<0.005	<1	4.60	<2	507	<2	<1	1.00	<4	17	152	38	2.98	0.49	26	1.12	385	15	127	407	16	0.47	<5	5	<10	268	2118	<2	70	<10	12	62
198785	1408984	<0.005	1	8.71	<2	613	2	6	1.44	<4	23	172	46	4.00	0.47	46	1.56	512	18	130	526	8	0.67	<5	<5	<10	306	3004	<2	102	<10	18	66
198786	1408985	<0.005	1	7.14	<2	663	<2	<1	1.25	<4	22	140	42	3.55	0.41	37	1.43	465	10	88	507	10	0.57	<5	<5	<10	321	2782	<2	92	<10	16	58
198787	1408986	<0.005	<1	7.33	<2	661	<2	<1	1.28	<4	22	193	43	3.64	0.56	38	1.45	474	13	114	516	14	0.58	<5	<5	<10	324	2760	4	93	<10	16	61
198788D	1408986	<0.005	1	7.31	<2	660	2	<1	1.27	<4	23	312	46	3.62	0.36	38	1.44	487	17	174	513	16	0.60	5	<5	<10	323	2815	<2	93	<10	16	60
198789	1408987	<0.005	<1	7.93	<2	549	2	2	1.44	<4	24	207	43	3.84	0.40	41	1.52	538	13	128	546	12	0.58	<5	5	<10	333	2913	<2	98	<10	18	61
198790	1408988	<0.005	1	7.85	<2	639	<2	<1	1.41	<4	24	195	48	4.08	0.24	41	1.60	520	14	129	533	23	0.57	<5	<5	<10	324	3019	5	103	11	18	113
198791	1408989	0.005	1	8.82	<2	678	2	5	1.40	4	25	198	42	4.28	0.27	46	1.68	547	17	144	544	8	0.60	<5	8	<10	316	3239	2	116	<10	19	63
198792	1408990	0.006	<1	>10.00	<2	564	2	2	1.71	4	25	210	49	4.32	0.36	48	1.67	572	20	158	548	13	0.75	<5	16	<10	346	3230	7	110	<10	21	77
198793	1408991	<0.005	<1	7.85	<2	587	2	<1	1.34	<4	24	199	48	4.06	0.37	40	1.56	534	17	147	534	16	0.56	<5	11	<10	313	2992	3	106	<10	18	73
198794	1408992	<0.005	2	8.86	<2	577	2	<1	1.46	<4	25	165	51	4.04	0.36	44	1.60	533	14	121	523	16	0.70	<5	6	<10	293	2997	3	106	<10	20	67
198795	1408993	<0.005	2	8.27	<2	525	<2	<1	1.50	<4	23	164	49	4.11	0.44	41	1.60	572	14	108	546	19	0.60	<5	<5	<10	298	2989	<2	106	<10	19	70
198796	1408994	<0.005	<1	>10.00	<2	539	2	12	1.39	<4	25	197	51	4.30	0.30	49	1.71	538	18	145	519	13	0.73	<5	5	<10	266	3169	2	116	<10	20	69
198797	1408995	<0.005	1	>10.00	<2	568	2	<1	1.40	4	26	171	45	4.60	0.41	51	1.81	530	17	120	507	9	0.77	<5	<5	<10	276	3177	2	123	<10	21	76

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 14, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/12/2012
 Date Completed: 08/01/2012
 Job #: 201242652
 Reference: TL 12 277
 Sample #: 311

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
198798	1408996	<0.005	<1	8.48	<2	551	2	<1	1.51	4	26	183	48	4.43	0.38	44	1.64	549	19	151	540	16	0.64	<5	7	<10	292	3037	6	109	<10	19	71
198799D	1408996	<0.005	2	9.25	<2	548	2	<1	1.58	4	24	174	47	4.33	0.44	46	1.65	541	19	140	537	15	0.70	<5	5	<10	296	3031	4	109	<10	19	67
198800	1408997	<0.005	<1	8.87	<2	573	2	<1	1.34	<4	25	174	47	4.37	0.38	46	1.70	532	19	137	529	15	0.67	<5	8	<10	274	3078	5	113	<10	19	67
198801	1408998	<0.005	2	7.57	<2	568	2	<1	1.25	<4	24	156	45	3.97	0.48	41	1.58	503	15	114	503	14	0.58	<5	<5	<10	293	2792	<2	100	<10	18	66
198802	1408999	<0.005	1	>10.00	4	613	2	5	1.98	<4	22	160	48	4.11	0.46	49	1.67	535	16	127	1329	17	0.71	<5	12	<10	356	2994	<2	108	144	20	68
198803	1409000	0.208	2	1.48	474	>5000	<2	<1	1.03	<4	5	17	33	2.85	0.34	10	0.27	<100	18	39	110	14	0.80	16	11	<10	129	756	6	16	44	10	18
198804	1369001	<0.005	1	7.15	<2	677	2	<1	1.25	<4	22	158	42	3.99	0.35	38	1.54	517	16	107	523	12	0.53	<5	<5	<10	310	2775	<2	101	<10	17	70
198805	1369002	<0.005	<1	6.90	<2	547	<2	<1	1.17	4	24	166	48	4.24	0.34	37	1.61	535	17	137	533	15	0.52	<5	<5	<10	278	2758	<2	106	10	17	73
198806	1369003	<0.005	<1	9.71	<2	570	2	<1	1.39	4	30	207	53	5.00	0.33	52	1.95	671	20	146	528	12	0.69	<5	11	<10	216	3432	<2	142	<10	23	76
198807	1369004	<0.005	<1	9.14	<2	597	2	2	1.02	4	28	197	70	5.04	0.35	53	1.96	588	19	147	525	18	1.91	<5	<5	<10	209	2650	<2	147	<10	21	92
198808	1369005	0.006	<1	8.50	<2	483	2	3	1.60	5	29	134	141	6.48	0.31	49	1.70	752	21	99	474	5	3.33	7	15	<10	186	2735	2	112	221	30	118
198809	1369006	<0.005	1	9.13	<2	479	2	5	1.19	6	28	128	148	6.57	0.38	49	1.69	716	22	95	467	4	3.47	<5	<5	<10	200	2742	2	110	12	23	208
198810D	1369006	<0.005	2	7.80	<2	479	2	9	1.06	6	30	133	147	6.75	0.39	45	1.67	732	20	96	476	7	3.47	<5	<5	<10	194	2746	3	112	<10	22	210
198811	1369007	0.016	2	6.39	<2	45	<2	10	7.22	8	38	211	57	9.78	0.41	28	3.52	3471	23	103	258	7	1.65	<5	<5	<10	170	3101	9	207	81	21	107
198812	1369008	0.038	2	6.51	3	42	<2	15	6.30	6	43	241	12	7.67	0.45	19	3.74	2382	18	92	254	3	0.42	5	6	<10	240	3491	9	244	<10	20	62
198813	1369009	0.022	<1	7.86	<2	36	<2	5	6.72	7	42	241	32	9.11	0.44	25	3.79	2725	22	92	260	4	0.79	<5	18	<10	148	3506	9	246	<10	21	73
198814	1369010	<0.005	2	8.13	<2	26	<2	5	7.17	6	40	260	77	7.08	0.44	19	3.58	1762	17	82	258	<1	0.48	6	9	<10	180	3914	5	260	<10	20	65
198815	1369011	0.006	3	6.71	<2	16	<2	8	6.82	6	39	178	61	6.87	0.47	16	3.14	1706	17	88	310	3	0.42	<5	9	<10	135	4493	7	278	<10	21	70
198816	1369012	<0.005	2	6.69	<2	20	<2	2	6.11	5	45	207	79	6.26	0.33	16	3.05	1414	17	88	314	<1	0.40	<5	<5	<10	121	4305	6	272	<10	20	72
198817	1369013	0.006	2	6.09	<2	11	<2	3	7.46	6	46	273	56	6.94	0.33	14	3.65	1587	14	110	212	4	0.30	<5	<5	<10	111	3308	18	227	<10	17	70

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 14, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/12/2012
 Date Completed: 08/01/2012
 Job #: 201242652
 Reference: TL 12 277
 Sample #: 311

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
198818	1369014	<0.005	1	7.84	<2	26	<2	6	7.35	6	47	287	86	6.83	0.34	20	3.59	1760	13	93	244	<1	0.41	<5	6	<10	120	3713	6	243	<10	18	69
198819	1369015	0.006	2	8.86	<2	37	<2	7	7.09	6	43	248	53	7.24	0.39	27	3.42	1915	20	134	252	7	0.63	<5	<5	<10	128	3430	5	222	<10	19	150
198820	1369016	0.011	2	7.69	<2	30	2	15	7.58	11	49	215	184	13.12	0.28	21	3.62	3555	29	111	265	4	1.90	5	5	<10	71	3290	7	221	<10	22	101
198821R	1369016	0.008	2	7.85	<2	31	2	10	6.97	10	47	216	185	12.90	0.39	22	3.60	3570	31	150	238	7	1.96	<5	<5	<10	69	3253	12	214	<10	22	95
198822	1369017	0.009	<1	7.46	<2	27	<2	4	7.93	8	47	244	81	10.21	0.27	14	3.44	2895	23	132	255	<1	0.75	<5	<5	<10	104	3590	13	240	<10	22	78
198823	1369018	0.008	4	8.53	<2	35	<2	14	7.47	7	44	261	53	8.42	0.43	20	3.09	2336	22	138	269	3	0.56	<5	<5	<10	125	3876	15	256	<10	22	71
198824	1369019	0.008	2	8.22	<2	43	<2	12	7.29	7	44	242	120	8.56	0.37	22	3.28	2284	18	137	251	2	0.70	<5	10	<10	107	3625	7	244	<10	20	74
198825	1369020	0.006	2	6.30	<2	437	<2	<1	2.65	<4	17	50	31	3.31	0.31	17	1.43	666	8	92	600	1	0.43	<5	<5	<10	313	2894	<2	119	20	18	54
198826	1369021	0.005	3	9.79	<2	45	<2	3	7.65	5	46	265	95	6.81	0.31	24	3.43	1380	18	117	264	<1	0.61	<5	<5	<10	141	3914	4	258	<10	21	84
198827	1369022	0.007	1	7.62	<2	27	<2	8	7.66	6	51	284	110	6.94	0.42	14	3.38	1393	16	164	258	3	0.50	<5	<5	<10	118	3917	3	250	<10	20	92
198828	1369023	0.012	1	8.48	<2	43	<2	<1	8.42	6	44	272	32	7.52	0.46	21	3.13	2143	20	129	272	<1	0.53	<5	<5	<10	130	3844	13	271	<10	22	64
198829	1369024	0.009	<1	8.08	<2	99	<2	<1	5.70	5	46	304	55	6.41	0.44	22	3.00	1836	19	173	245	2	0.64	<5	9	<10	130	3704	9	236	<10	18	62
198830	1369025	<0.005	<1	8.51	<2	178	<2	6	4.67	4	45	288	79	5.11	0.46	26	3.15	1380	13	143	279	2	0.55	<5	<5	<10	180	3672	6	219	<10	17	55
198831	1369026	0.006	1	8.65	<2	226	2	6	4.68	5	45	275	94	5.17	0.32	25	3.02	1349	15	151	333	<1	0.60	<5	5	<10	196	3624	10	213	<10	19	78
198832D	1369026	0.006	4	9.65	<2	231	<2	11	4.95	4	46	285	98	5.37	0.34	29	3.15	1393	13	158	353	7	0.65	<5	<5	<10	206	3754	2	219	<10	18	73
198833	1369027	<0.005	2	8.44	<2	231	<2	<1	6.57	5	46	330	73	6.77	0.33	22	2.90	1712	21	202	326	3	0.62	<5	<5	<10	223	3441	24	206	<10	18	66
198834	1369028	0.006	<1	6.87	<2	94	<2	<1	7.01	7	53	500	76	7.96	0.28	18	3.17	2156	19	233	228	4	0.49	<5	<5	<10	114	3401	10	224	<10	18	71
198835	1369029	0.007	<1	8.79	<2	101	2	2	7.04	7	56	496	100	8.70	0.42	29	3.54	2232	22	196	245	<1	0.62	<5	12	<10	118	3649	10	244	<10	21	73
198836	1369030	0.006	4	7.39	<2	95	<2	2	7.09	7	60	540	71	7.90	0.42	26	3.31	2014	18	232	232	4	0.45	<5	<5	<10	123	3789	18	251	<10	20	72
198837	1369031	<0.005	3	8.20	<2	71	<2	3	6.78	6	65	589	51	7.50	0.40	20	3.30	2022	17	266	265	7	0.42	<5	<5	<10	120	4211	7	272	<10	22	78

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 14, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/12/2012
 Date Completed: 08/01/2012
 Job #: 201242652
 Reference: TL 12 277
 Sample #: 311

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
198838	1369032	0.006	<1	7.27	<2	56	<2	7	7.72	6	56	522	46	8.07	0.47	16	3.24	2183	20	223	238	6	0.42	<5	<5	<10	112	3520	11	237	<10	20	71
198839	1369033	0.007	<1	7.86	<2	66	<2	4	7.46	7	54	499	90	9.27	0.47	21	3.52	2638	24	202	233	2	0.50	<5	13	<10	98	3460	16	230	<10	20	73
198840	1369034	0.013	<1	6.42	<2	89	<2	6	6.91	6	57	509	68	7.69	0.47	16	3.08	2141	19	209	226	3	0.40	<5	<5	<10	118	3422	13	229	<10	18	66
198841	1369035	<0.005	<1	7.55	<2	84	<2	6	6.85	7	54	445	65	8.39	0.52	20	3.30	2249	20	186	239	<1	0.53	<5	10	<10	140	3552	9	233	<10	20	73
198842	1369036	0.006	5	5.94	<2	64	<2	<1	6.25	6	46	96	131	8.04	0.43	18	3.23	1656	18	114	305	4	0.53	<5	<5	<10	127	4568	<2	292	<10	21	81
198843D	1369036	<0.005	7	7.16	<2	72	<2	2	6.34	6	46	89	134	8.02	0.33	22	3.25	1639	20	121	317	1	0.62	<5	5	<10	136	4548	14	293	<10	22	80
198844	1369037	0.005	3	8.85	<2	85	<2	2	6.34	7	48	84	129	8.21	0.37	28	3.34	1661	19	125	366	1	0.68	<5	7	<10	142	4840	19	306	<10	24	83
198845	1369038	<0.005	3	8.37	<2	87	<2	<1	6.69	6	46	142	127	7.94	0.29	26	3.52	1653	20	124	351	6	0.60	<5	<5	<10	135	4806	5	298	<10	23	87
198846	1369039	<0.005	4	8.18	<2	178	<2	7	6.35	7	46	43	173	8.96	0.28	27	2.96	1938	24	103	433	2	0.83	<5	6	<10	113	5680	3	341	<10	27	91
198847	1369040	2.021	1	8.29	3	463	<2	<1	2.76	<4	18	51	39	3.71	0.32	25	1.53	708	10	81	631	4	0.55	6	<5	<10	314	3064	6	127	24	20	59
198848	1369041	0.007	1	7.13	<2	54	<2	5	6.91	6	45	226	108	6.76	0.37	15	3.43	1419	18	126	272	7	0.48	<5	6	<10	127	3795	12	256	<10	18	68
198849	1369042	<0.005	1	8.13	<2	36	<2	<1	6.37	5	42	210	77	6.75	0.44	25	3.85	1117	16	137	282	<1	0.55	<5	11	<10	113	3363	6	229	<10	18	68
198850	1369043	<0.005	<1	8.34	<2	33	<2	<1	7.47	6	42	211	53	7.25	0.42	19	3.57	1370	18	134	256	<1	0.50	<5	<5	<10	122	3636	9	246	<10	18	53
198851	1369044	<0.005	2	7.27	<2	60	<2	<1	6.95	6	44	102	55	7.70	0.32	14	3.26	1378	18	120	284	<1	0.41	<5	8	<10	119	4049	<2	273	<10	20	59
198852	1369045	<0.005	6	8.47	<2	83	<2	9	6.30	6	43	48	65	8.10	0.42	22	2.76	1498	24	120	331	<1	0.56	<5	5	<10	126	4404	4	283	<10	23	68
198853	1369046	<0.005	7	8.59	<2	82	<2	3	6.59	7	47	42	78	8.44	0.44	22	2.86	1549	23	120	342	5	0.55	<5	<5	<10	129	4702	17	298	<10	24	73
198854D	1369046	<0.005	3	9.28	<2	87	<2	6	6.84	7	49	44	80	8.69	0.48	24	2.96	1603	25	123	360	4	0.59	<5	<5	<10	136	4843	6	308	<10	25	75
198855	1369047	<0.005	5	8.42	<2	77	<2	8	6.21	7	48	24	42	8.60	0.29	19	2.76	1552	22	107	372	7	0.53	<5	10	<10	124	5288	6	323	<10	26	62
198856	1369048	<0.005	6	7.64	<2	47	<2	<1	6.78	6	42	24	15	8.08	0.33	13	2.58	1251	21	111	387	5	0.45	<5	8	<10	136	5400	<2	333	<10	26	37
198857	1369049	<0.005	5	7.88	<2	41	<2	<1	6.49	7	44	16	49	8.49	0.26	15	2.48	1448	21	91	377	2	0.50	<5	6	<10	129	5358	5	326	<10	26	55

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 14, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/12/2012
 Date Completed: 08/01/2012
 Job #: 201242652
 Reference: TL 12 277
 Sample #: 311

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
198858	1369050	0.024	4	7.50	<2	55	<2	<1	7.13	6	43	141	82	7.47	0.31	19	3.40	1337	15	105	277	<1	0.51	<5	<5	<10	123	3929	15	262	<10	20	52
198859	1369051	0.017	2	7.00	<2	33	<2	<1	7.40	5	43	80	64	6.54	0.30	15	4.12	1300	11	135	192	<1	0.42	<5	10	<10	114	2807	18	216	<10	15	52
198860	1369052	<0.005	<1	6.02	<2	27	<2	2	7.25	5	45	243	59	6.01	0.36	16	4.55	1185	6	142	165	1	0.33	<5	<5	<10	102	2240	4	181	<10	12	45
198861	1369053	<0.005	2	8.01	<2	57	<2	<1	7.74	4	38	714	101	5.63	0.32	19	4.29	1073	10	133	164	<1	0.46	<5	5	<10	127	2200	10	179	<10	13	44
198862	1369054	0.005	2	7.78	<2	42	<2	2	7.39	5	40	348	111	6.38	0.30	20	3.72	1082	14	99	245	4	0.53	<5	8	<10	128	3128	<2	217	<10	17	50
198863	1369055	<0.005	<1	7.56	<2	73	<2	<1	7.52	5	32	223	56	5.78	0.28	11	3.44	915	12	110	277	2	0.47	7	6	<10	118	3609	13	247	<10	18	41
198864	1369056	<0.005	1	6.95	<2	61	<2	6	6.88	6	44	367	49	6.75	0.39	16	4.19	1050	13	157	259	2	0.43	<5	<5	<10	120	3380	11	235	<10	17	52
198865D	1369056	<0.005	<1	5.86	<2	54	<2	<1	6.62	5	43	362	50	6.62	0.37	13	4.11	1035	14	161	252	<1	0.36	<5	9	<10	110	3293	6	229	<10	16	53
198866	1369057	0.007	<1	7.70	<2	79	<2	9	6.29	6	52	485	72	7.54	0.48	27	4.99	1306	14	199	227	2	0.52	<5	<5	<10	97	3158	10	221	<10	17	63
198867	1369058	<0.005	2	6.93	<2	32	<2	1	6.66	6	43	245	75	7.15	0.31	13	3.67	1173	15	120	242	2	0.42	<5	<5	<10	108	3299	8	236	<10	17	58
198868	1369059	0.009	2	8.08	<2	67	<2	1	5.76	7	49	178	96	8.77	0.23	25	3.49	1268	21	120	287	4	0.57	<5	7	<10	107	3854	14	263	<10	20	74
198869	1369060	<0.005	1	6.43	<2	432	<2	<1	2.71	<4	17	52	26	3.40	0.19	17	1.46	678	8	54	600	5	0.44	<5	9	<10	315	2986	10	122	21	18	51
198870	1369061	<0.005	3	6.63	<2	27	<2	<1	6.85	6	45	287	50	7.34	0.25	14	3.93	1197	15	140	242	2	0.37	<5	<5	<10	135	3363	16	242	<10	18	47
198871	1369062	<0.005	<1	7.90	<2	26	<2	13	7.18	6	51	327	34	8.12	0.30	20	4.40	1340	14	157	293	3	0.45	<5	10	<10	142	3609	<2	280	<10	23	59
198872	1369063	<0.005	<1	6.89	<2	25	<2	4	6.29	7	64	735	27	8.28	0.33	26	6.01	1373	13	281	237	4	0.42	<5	<5	<10	114	3185	<2	226	<10	18	66
198873	1369064	<0.005	3	3.60	<2	11	<2	<1	5.09	6	72	1078	47	8.00	0.30	32	7.16	1283	4	386	178	5	0.31	<5	8	<10	40	2198	4	178	<10	12	74
198874	1369065	<0.005	1	7.28	<2	62	<2	13	4.98	6	59	855	48	8.01	0.46	45	6.16	1314	10	278	199	<1	0.47	<5	<5	<10	83	2677	<2	209	<10	16	66
198875	1369066	<0.005	<1	5.32	<2	43	<2	8	4.60	6	58	824	50	7.62	0.42	40	5.86	1264	9	269	184	<1	0.38	<5	11	<10	65	2453	10	198	<10	14	61
198876D	1369066	<0.005	1	5.53	<2	44	<2	<1	4.70	6	57	839	52	7.75	0.39	41	5.95	1287	12	278	190	<1	0.38	<5	<5	<10	66	2514	<2	202	<10	14	63
198877	1369067	<0.005	2	5.95	<2	41	<2	11	4.98	6	61	683	139	8.14	0.49	34	5.49	1216	9	237	191	4	0.53	<5	<5	<10	88	2616	9	211	<10	15	59

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 14, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/12/2012
 Date Completed: 08/01/2012
 Job #: 201242652
 Reference: TL 12 277
 Sample #: 311

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
198878	1369068	<0.005	1	7.48	<2	44	<2	3	5.65	5	40	323	94	6.33	0.45	27	3.96	1097	12	109	198	<1	0.56	5	5	<10	153	2858	6	223	<10	17	50
198879	1369069	<0.005	2	8.30	<2	44	<2	8	6.70	5	43	208	52	7.15	0.39	26	4.12	1203	16	125	214	<1	0.54	<5	5	<10	184	3241	13	258	<10	18	37
198880	1369070	<0.005	2	7.13	<2	30	3	6	9.40	6	42	149	39	6.89	0.26	14	3.93	1388	27	123	836	6	0.46	5	8	<10	219	3221	9	254	239	21	43
198881	1369071	<0.005	2	8.13	<2	40	<2	2	6.97	6	43	96	43	7.33	0.26	22	3.64	1261	16	111	278	<1	0.54	<5	<5	<10	184	3525	10	272	<10	20	45
198882	1369072	<0.005	3	7.82	<2	37	<2	<1	6.99	6	44	84	47	7.48	0.28	19	3.58	1308	18	126	250	<1	0.49	<5	<5	<10	179	3301	8	267	<10	19	51
198883	1369073	<0.005	5	8.75	<2	43	<2	4	6.63	7	48	44	91	8.39	0.34	28	3.40	1413	22	123	299	6	0.60	<5	5	<10	200	4061	3	300	<10	22	53
198884	1369074	<0.005	6	6.57	<2	40	<2	6	6.11	7	49	331	104	8.62	0.34	20	3.00	1451	28	302	312	6	0.51	<5	<5	<10	164	4248	11	310	<10	22	97
198885	1369075	<0.005	5	5.46	<2	38	<2	4	6.54	7	44	21	52	8.60	0.30	21	2.68	1420	19	123	328	4	0.35	<5	7	<10	213	4488	3	326	100	23	85
198886	1369076	0.010	3	6.81	<2	36	<2	2	6.13	8	48	17	122	10.07	0.35	20	2.27	1534	25	133	421	<1	0.59	<5	<5	<10	185	5622	<2	375	<10	30	87
198887R	1369076	<0.005	5	6.47	<2	31	2	10	6.03	8	48	17	124	9.89	0.36	18	2.21	1505	23	140	416	3	0.58	<5	<5	<10	182	5514	5	368	<10	29	71
198888	1369077	0.009	3	6.47	<2	27	<2	<1	5.96	8	43	15	81	9.31	0.31	31	1.51	1399	22	118	523	3	0.63	<5	12	<10	306	5434	<2	268	<10	35	175
198889	1369078	<0.005	5	6.94	<2	52	<2	3	5.58	8	46	17	52	9.63	0.36	22	1.95	1410	23	133	421	7	0.49	<5	<5	<10	183	5506	5	375	21	29	65
198890	1369079	<0.005	4	5.94	<2	53	<2	2	5.22	8	47	12	41	9.70	0.36	16	1.87	1385	21	109	418	8	0.45	<5	<5	<10	131	5416	<2	372	<10	29	64
198891	1369080	5.444	69	4.81	25	476	<2	<1	1.49	20	14	31	62	3.08	0.34	14	0.91	485	10	99	534	541	0.71	59	7	209	254	1978	4	93	51	15	1799
198892	1369081	<0.005	5	6.04	<2	49	<2	3	5.81	7	51	42	112	9.33	0.43	26	2.03	1341	21	116	754	2	0.87	<5	<5	<10	202	7102	4	266	<10	38	67
198893	1369082	<0.005	4	5.51	<2	49	2	10	6.05	9	57	27	116	10.53	0.40	16	2.16	1608	22	119	868	1	0.74	<5	10	<10	217	8507	<2	350	<10	41	124
198894	1369083	0.005	5	6.04	<2	106	2	<1	5.66	8	57	26	134	10.44	0.38	16	2.34	1716	22	102	820	6	0.84	<5	<5	<10	155	8444	4	346	<10	41	134
198895	1369084	<0.005	3	5.64	<2	64	2	6	5.84	9	57	32	125	10.85	0.42	16	2.37	1733	23	116	885	1	0.59	<5	<5	<10	176	8184	7	346	<10	41	149
198896	1369085	<0.005	5	6.39	<2	65	2	1	5.94	9	56	27	98	11.15	0.40	16	2.36	1598	24	113	891	5	0.66	5	11	<10	194	8627	2	362	<10	42	113
198897	1369086	<0.005	5	6.96	<2	62	2	3	6.03	9	57	26	124	11.03	0.30	18	2.34	1586	25	112	845	2	0.73	8	6	<10	205	8694	2	356	<10	42	114

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, August 14, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/12/2012
 Date Completed: 08/01/2012
 Job #: 201242652
 Reference: TL 12 277
 Sample #: 311

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
198898D	1369086	<0.005	6	6.85	<2	59	2	<1	6.12	9	61	27	126	11.30	0.24	17	2.38	1641	24	111	856	7	0.72	<5	<5	<10	207	9215	7	364	<10	42	124
198899	1369087	<0.005	5	6.62	<2	35	2	5	5.14	10	57	29	98	11.97	0.17	22	2.67	1617	27	101	946	5	0.62	<5	<5	<10	166	9121	10	393	<10	44	129

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Wednesday, August 1, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/12/2012
 Date Completed: 08/01/2012
 Job #: 201242652
 Reference: TL 12 277
 Sample #: 311

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
198558	1408777	<5	<0.001	<0.005
198559	1408778	<5	<0.001	<0.005
198560	1408779	<5	<0.001	<0.005
198561	1408780	<5	<0.001	<0.005
198562	1408781	<5	<0.001	<0.005
198563	1408782	<5	<0.001	<0.005
198564	1408783	<5	<0.001	<0.005
198565	1408784	6	<0.001	0.006
198566	1408785	<5	<0.001	<0.005
198567	1408786	<5	<0.001	<0.005
198568 Dup	1408786	<5	<0.001	<0.005
198569	1408787	9	<0.001	0.009
198570	1408788	<5	<0.001	<0.005
198571	1408789	<5	<0.001	<0.005
198572	1408790	<5	<0.001	<0.005
198573	1408791	<5	<0.001	<0.005
198574	1408792	<5	<0.001	<0.005
198575	1408793	<5	<0.001	<0.005
198576	1408794	<5	<0.001	<0.005
198577	1408795	<5	<0.001	<0.005
198578	1408796	<5	<0.001	<0.005
198579 Dup	1408796	<5	<0.001	<0.005
198580	1408797	<5	<0.001	<0.005
198581	1408798	<5	<0.001	<0.005
198582	1408799	<5	<0.001	<0.005
198583	1408800	4990	0.146	4.990
198584	1408801	<5	<0.001	<0.005
198585	1408802	<5	<0.001	<0.005
198586	1408803	<5	<0.001	<0.005
198587	1408804	12	<0.001	0.012

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, August 1, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/12/2012
 Date Completed: 08/01/2012
 Job #: 201242652
 Reference: TL 12 277
 Sample #: 311

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
198588	1408805	<5	<0.001	<0.005
198589	1408806	<5	<0.001	<0.005
198590 Dup	1408806	<5	<0.001	<0.005
198591	1408807	<5	<0.001	<0.005
198592	1408808	<5	<0.001	<0.005
198593	1408809	<5	<0.001	<0.005
198594	1408810	13	<0.001	0.013
198595	1408811	<5	<0.001	<0.005
198596	1408812	<5	<0.001	<0.005
198597	1408813	<5	<0.001	<0.005
198598	1408814	<5	<0.001	<0.005
198599	1408815	<5	<0.001	<0.005
198600	1408816	<5	<0.001	<0.005
198601 Dup	1408816	<5	<0.001	<0.005
198602	1408817	<5	<0.001	<0.005
198603	1408818	<5	<0.001	<0.005
198604	1408819	<5	<0.001	<0.005
198605	1408820	<5	<0.001	<0.005
198606	1408821	<5	<0.001	<0.005
198607	1408822	<5	<0.001	<0.005
198608	1408823	<5	<0.001	<0.005
198609	1408824	<5	<0.001	<0.005
198610	1408825	<5	<0.001	<0.005
198611	1408826	<5	<0.001	<0.005
198612 Dup	1408826	<5	<0.001	<0.005
198613	1408827	6	<0.001	0.006
198614	1408828	7	<0.001	0.007
198615	1408829	9	<0.001	0.009
198616	1408830	9	<0.001	0.009
198617	1408831	9	<0.001	0.009

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, August 1, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/12/2012
 Date Completed: 08/01/2012
 Job #: 201242652
 Reference: TL 12 277
 Sample #: 311

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
198618	1408832	9	<0.001	0.009
198619	1408833	<5	<0.001	<0.005
198620	1408834	7	<0.001	0.007
198621	1408835	5	<0.001	0.005
198622	1408836	5	<0.001	0.005
198623 Rep	1408836	9	<0.001	0.009
198624	1408837	9	<0.001	0.009
198625	1408838	8	<0.001	0.008
198626	1408839	11	<0.001	0.011
198627	1408840	1842	0.054	1.842
198628	1408841	8	<0.001	0.008
198629	1408842	9	<0.001	0.009
198630	1408843	7	<0.001	0.007
198631	1408844	8	<0.001	0.008
198632	1408845	9	<0.001	0.009
198633	1408846	<5	<0.001	<0.005
198634 Dup	1408846	<5	<0.001	<0.005
198635	1408847	<5	<0.001	<0.005
198636	1408848	<5	<0.001	<0.005
198637	1408849	<5	<0.001	<0.005
198638	1408850	<5	<0.001	<0.005
198639	1408851	5	<0.001	0.005
198640	1408852	<5	<0.001	<0.005
198641	1408853	7	<0.001	0.007
198642	1408854	6	<0.001	0.006
198643	1408855	6	<0.001	0.006
198644	1408856	9	<0.001	0.009
198645 Dup	1408856	8	<0.001	0.008
198646	1408857	6	<0.001	0.006
198647	1408858	5	<0.001	0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, August 1, 2012

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/12/2012
 Date Completed: 08/01/2012
 Job #: 201242652
 Reference: TL 12 277
 Sample #: 311

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
198648	1408859	11	<0.001	0.011
198649	1408860	<5	<0.001	<0.005
198650	1408861	8	<0.001	0.008
198651	1408862	13	<0.001	0.013
198652	1408863	7	<0.001	0.007
198653	1408864	6	<0.001	0.006
198654	1408865	6	<0.001	0.006
198655	1408866	<5	<0.001	<0.005
198656 Dup	1408866	<5	<0.001	<0.005
198657	1408867	<5	<0.001	<0.005
198658	1408868	<5	<0.001	<0.005
198659	1408869	7	<0.001	0.007
198660	1408870	6	<0.001	0.006
198661	1408871	<5	<0.001	<0.005
198662	1408872	<5	<0.001	<0.005
198663	1408873	<5	<0.001	<0.005
198664	1408874	<5	<0.001	<0.005
198665	1408875	<5	<0.001	<0.005
198666	1408876	7	<0.001	0.007
198667 Dup	1408876	6	<0.001	0.006
198668	1408877	<5	<0.001	<0.005
198669	1408878	<5	<0.001	<0.005
198670	1408879	7	<0.001	0.007
198671	1408880	243	0.007	0.243
198672	1408881	7	<0.001	0.007
198673	1408882	7	<0.001	0.007
198674	1408883	6	<0.001	0.006
198675	1408884	6	<0.001	0.006
198676	1408885	<5	<0.001	<0.005
198677	1408886	6	<0.001	0.006

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, August 1, 2012

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/12/2012
 Date Completed: 08/01/2012
 Job #: 201242652
 Reference: TL 12 277
 Sample #: 311

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
198678 Dup	1408886	6	<0.001	0.006
198679	1408887	6	<0.001	0.006
198680	1408888	7	<0.001	0.007
198681	1408889	9	<0.001	0.009
198682	1408890	9	<0.001	0.009
198683	1408891	11	<0.001	0.011
198684	1408892	6	<0.001	0.006
198685	1408893	8	<0.001	0.008
198686	1408894	10	<0.001	0.010
198687	1408895	8	<0.001	0.008
198688	1408896	8	<0.001	0.008
198689 Rep	1408896	8	<0.001	0.008
198690	1408897	8	<0.001	0.008
198691	1408898	11	<0.001	0.011
198692	1408899	7	<0.001	0.007
198693	1408900	<5	<0.001	<0.005
198694	1408901	11	<0.001	0.011
198695	1408902	<5	<0.001	<0.005
198696	1408903	<5	<0.001	<0.005
198697	1408904	6	<0.001	0.006
198698	1408905	<5	<0.001	<0.005
198699	1408906	<5	<0.001	<0.005
198700 Dup	1408906	7	<0.001	0.007
198701	1408907	5	<0.001	0.005
198702	1408908	<5	<0.001	<0.005
198703	1408909	<5	<0.001	<0.005
198704	1408910	5	<0.001	0.005
198705	1408911	<5	<0.001	<0.005
198706	1408912	6	<0.001	0.006
198707	1408913	5	<0.001	0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, August 1, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/12/2012
 Date Completed: 08/01/2012
 Job #: 201242652
 Reference: TL 12 277
 Sample #: 311

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
198708	1408914	8	<0.001	0.008
198709	1408915	5	<0.001	0.005
198710	1408916	12	<0.001	0.012
198711 Dup	1408916	11	<0.001	0.011
198712	1408917	7	<0.001	0.007
198713	1408918	8	<0.001	0.008
198714	1408919	9	<0.001	0.009
198715	1408920	5372	0.157	5.372
198716	1408921	5	<0.001	0.005
198717	1408922	10	<0.001	0.010
198718	1408923	10	<0.001	0.010
198719	1408924	9	<0.001	0.009
198720	1408925	11	<0.001	0.011
198721	1408926	8	<0.001	0.008
198722 Dup	1408926	10	<0.001	0.010
198723	1408927	10	<0.001	0.010
198724	1408928	10	<0.001	0.010
198725	1408929	11	<0.001	0.011
198726	1408930	12	<0.001	0.012
198727	1408931	10	<0.001	0.010
198728	1408932	10	<0.001	0.010
198729	1408933	6	<0.001	0.006
198730	1408934	6	<0.001	0.006
198731	1408935	14	<0.001	0.014
198732	1408936	6	<0.001	0.006
198733 Dup	1408936	8	<0.001	0.008
198734	1408937	8	<0.001	0.008
198735	1408938	8	<0.001	0.008
198736	1408939	20	<0.001	0.020
198737	1408940	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, August 1, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/12/2012
 Date Completed: 08/01/2012
 Job #: 201242652
 Reference: TL 12 277
 Sample #: 311

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
198738	1408941	9	<0.001	0.009
198739	1408942	8	<0.001	0.008
198740	1408943	9	<0.001	0.009
198741	1408944	7	<0.001	0.007
198742	1408945	5	<0.001	0.005
198743	1408946	7	<0.001	0.007
198744 Dup	1408946	7	<0.001	0.007
198745	1408947	<5	<0.001	<0.005
198746	1408948	5	<0.001	0.005
198747	1408949	9	<0.001	0.009
198748	1408950	9	<0.001	0.009
198749	1408951	6	<0.001	0.006
198750	1408952	6	<0.001	0.006
198751	1408953	<5	<0.001	<0.005
198752	1408954	6	<0.001	0.006
198753	1408955	6	<0.001	0.006
198754	1408956	6	<0.001	0.006
198755 Rep	1408956	6	<0.001	0.006
198756	1408957	8	<0.001	0.008
198757	1408958	6	<0.001	0.006
198758	1408959	7	<0.001	0.007
198759	1408960	1743	0.051	1.743
198760	1408961	18	<0.001	0.018
198761	1408962	8	<0.001	0.008
198762	1408963	5	<0.001	0.005
198763	1408964	6	<0.001	0.006
198764	1408965	9	<0.001	0.009
198765	1408966	9	<0.001	0.009
198766 Dup	1408966	8	<0.001	0.008
198767	1408967	11	<0.001	0.011

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, August 1, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/12/2012
 Date Completed: 08/01/2012
 Job #: 201242652
 Reference: TL 12 277
 Sample #: 311

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
198768	1408968	8	<0.001	0.008
198769	1408969	7	<0.001	0.007
198770	1408970	8	<0.001	0.008
198771	1408971	8	<0.001	0.008
198772	1408972	7	<0.001	0.007
198773	1408973	6	<0.001	0.006
198774	1408974	7	<0.001	0.007
198775	1408975	7	<0.001	0.007
198776	1408976	6	<0.001	0.006
198777 Dup	1408976	8	<0.001	0.008
198778	1408977	8	<0.001	0.008
198779	1408978	<5	<0.001	<0.005
198780	1408979	<5	<0.001	<0.005
198781	1408980	<5	<0.001	<0.005
198782	1408981	<5	<0.001	<0.005
198783	1408982	<5	<0.001	<0.005
198784	1408983	<5	<0.001	<0.005
198785	1408984	<5	<0.001	<0.005
198786	1408985	<5	<0.001	<0.005
198787	1408986	<5	<0.001	<0.005
198788 Dup	1408986	<5	<0.001	<0.005
198789	1408987	<5	<0.001	<0.005
198790	1408988	<5	<0.001	<0.005
198791	1408989	5	<0.001	0.005
198792	1408990	6	<0.001	0.006
198793	1408991	<5	<0.001	<0.005
198794	1408992	<5	<0.001	<0.005
198795	1408993	<5	<0.001	<0.005
198796	1408994	<5	<0.001	<0.005
198797	1408995	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, August 1, 2012

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/12/2012
 Date Completed: 08/01/2012
 Job #: 201242652
 Reference: TL 12 277
 Sample #: 311

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
198798	1408996	<5	<0.001	<0.005
198799 Dup	1408996	<5	<0.001	<0.005
198800	1408997	<5	<0.001	<0.005
198801	1408998	<5	<0.001	<0.005
198802	1408999	<5	<0.001	<0.005
198803	1409000	208	0.006	0.208
198804	1369001	<5	<0.001	<0.005
198805	1369002	<5	<0.001	<0.005
198806	1369003	<5	<0.001	<0.005
198807	1369004	<5	<0.001	<0.005
198808	1369005	6	<0.001	0.006
198809	1369006	<5	<0.001	<0.005
198810 Dup	1369006	<5	<0.001	<0.005
198811	1369007	16	<0.001	0.016
198812	1369008	38	0.001	0.038
198813	1369009	22	<0.001	0.022
198814	1369010	<5	<0.001	<0.005
198815	1369011	6	<0.001	0.006
198816	1369012	<5	<0.001	<0.005
198817	1369013	6	<0.001	0.006
198818	1369014	<5	<0.001	<0.005
198819	1369015	6	<0.001	0.006
198820	1369016	11	<0.001	0.011
198821 Rep	1369016	8	<0.001	0.008
198822	1369017	9	<0.001	0.009
198823	1369018	8	<0.001	0.008
198824	1369019	8	<0.001	0.008
198825	1369020	6	<0.001	0.006
198826	1369021	5	<0.001	0.005
198827	1369022	7	<0.001	0.007

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, August 1, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/12/2012
 Date Completed: 08/01/2012
 Job #: 201242652
 Reference: TL 12 277
 Sample #: 311

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
198828	1369023	12	<0.001	0.012
198829	1369024	9	<0.001	0.009
198830	1369025	<5	<0.001	<0.005
198831	1369026	6	<0.001	0.006
198832 Dup	1369026	6	<0.001	0.006
198833	1369027	<5	<0.001	<0.005
198834	1369028	6	<0.001	0.006
198835	1369029	7	<0.001	0.007
198836	1369030	6	<0.001	0.006
198837	1369031	<5	<0.001	<0.005
198838	1369032	6	<0.001	0.006
198839	1369033	7	<0.001	0.007
198840	1369034	13	<0.001	0.013
198841	1369035	<5	<0.001	<0.005
198842	1369036	6	<0.001	0.006
198843 Dup	1369036	<5	<0.001	<0.005
198844	1369037	5	<0.001	0.005
198845	1369038	<5	<0.001	<0.005
198846	1369039	<5	<0.001	<0.005
198847	1369040	2021	0.059	2.021
198848	1369041	7	<0.001	0.007
198849	1369042	<5	<0.001	<0.005
198850	1369043	<5	<0.001	<0.005
198851	1369044	<5	<0.001	<0.005
198852	1369045	<5	<0.001	<0.005
198853	1369046	<5	<0.001	<0.005
198854 Dup	1369046	<5	<0.001	<0.005
198855	1369047	<5	<0.001	<0.005
198856	1369048	<5	<0.001	<0.005
198857	1369049	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, August 1, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/12/2012
 Date Completed: 08/01/2012
 Job #: 201242652
 Reference: TL 12 277
 Sample #: 311

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
198858	1369050	24	<0.001	0.024
198859	1369051	17	<0.001	0.017
198860	1369052	<5	<0.001	<0.005
198861	1369053	<5	<0.001	<0.005
198862	1369054	5	<0.001	0.005
198863	1369055	<5	<0.001	<0.005
198864	1369056	<5	<0.001	<0.005
198865 Dup	1369056	<5	<0.001	<0.005
198866	1369057	7	<0.001	0.007
198867	1369058	<5	<0.001	<0.005
198868	1369059	9	<0.001	0.009
198869	1369060	<5	<0.001	<0.005
198870	1369061	<5	<0.001	<0.005
198871	1369062	<5	<0.001	<0.005
198872	1369063	<5	<0.001	<0.005
198873	1369064	<5	<0.001	<0.005
198874	1369065	<5	<0.001	<0.005
198875	1369066	<5	<0.001	<0.005
198876 Dup	1369066	<5	<0.001	<0.005
198877	1369067	<5	<0.001	<0.005
198878	1369068	<5	<0.001	<0.005
198879	1369069	<5	<0.001	<0.005
198880	1369070	<5	<0.001	<0.005
198881	1369071	<5	<0.001	<0.005
198882	1369072	<5	<0.001	<0.005
198883	1369073	<5	<0.001	<0.005
198884	1369074	<5	<0.001	<0.005
198885	1369075	<5	<0.001	<0.005
198886	1369076	10	<0.001	0.010
198887 Rep	1369076	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Wednesday, August 1, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 07/12/2012
 Date Completed: 08/01/2012
 Job #: 201242652
 Reference: TL 12 277
 Sample #: 311

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
198888	1369077	9	<0.001	0.009
198889	1369078	<5	<0.001	<0.005
198890	1369079	<5	<0.001	<0.005
198891	1369080	5444	0.159	5.444
198892	1369081	<5	<0.001	<0.005
198893	1369082	<5	<0.001	<0.005
198894	1369083	5	<0.001	0.005
198895	1369084	<5	<0.001	<0.005
198896	1369085	<5	<0.001	<0.005
198897	1369086	<5	<0.001	<0.005
198898 Dup	1369086	<5	<0.001	<0.005
198899	1369087	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.
 The results generated by this procedure are not accredited at this time and therefore are informational only.

Saturday, November 24, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 11/06/2012
 Date Completed: 11/16/2012
 Job #: 201244235
 Reference: TL12-278
 Sample #: 110

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
307860	1366055	<0.005	<1	2.67	<2	358	<2	<1	1.97	<4	10	22	10	1.83	<0.01	7	0.68	355	<1	25	475	10	0.55	<5	<5	<10	308	1818	<2	40	<10	5	49
307861	1366056	0.005	<1	3.20	<2	352	<2	4	1.95	<4	10	13	9	1.84	<0.01	7	0.62	335	<1	34	484	9	0.63	<5	<5	<10	338	1815	<2	38	<10	5	50
307862	1366057	<0.005	<1	3.16	5	468	<2	<1	1.54	<4	9	17	10	1.93	<0.01	9	0.70	489	<1	29	454	14	1.22	<5	<5	<10	335	1568	<2	35	<10	5	59
307863	1366058	0.014	<1	5.75	3	649	<2	5	1.96	<4	9	13	23	1.97	<0.01	15	0.65	396	<1	35	417	25	1.56	<5	<5	<10	448	1447	<2	33	<10	7	232
307864	1366059	0.006	<1	3.59	4	588	<2	10	2.00	<4	8	10	12	1.71	<0.01	8	0.63	303	<1	28	481	15	0.40	<5	<5	<10	361	1763	<2	39	<10	5	60
307865	1366060	4.844	66	1.89	32	392	<2	<1	1.23	22	14	27	50	3.05	<0.01	4	0.82	481	<1	34	508	591	0.42	34	<5	226	195	1668	<2	88	58	12	1824
307866	1366061	0.096	2	3.57	15	538	<2	<1	1.88	5	12	30	23	2.48	<0.01	8	1.10	1081	<1	39	545	855	1.62	<5	<5	<10	263	1802	<2	46	16	6	1021
307867	1366062	0.088	1	3.75	15	513	<2	2	1.90	5	8	19	55	1.70	<0.01	7	1.04	1109	<1	30	469	95	1.05	<5	8	<10	145	1477	<2	34	20	5	1157
307868	1366063	0.106	<1	3.55	22	454	<2	9	2.02	<4	8	12	37	1.80	0.16	6	1.04	1026	<1	31	458	57	1.17	<5	<5	<10	158	1557	<2	34	<10	5	324
307869	1366064	0.051	<1	3.80	10	473	<2	<1	2.88	<4	8	13	28	1.78	<0.01	7	1.29	1492	<1	28	458	20	0.78	<5	<5	<10	177	1765	<2	36	<10	5	163
307870D	1366064	0.053	<1	3.68	11	461	<2	1	2.85	<4	9	13	28	1.78	0.04	7	1.28	1482	<1	29	456	20	0.80	<5	10	<10	174	1778	<2	35	<10	5	159
307871	1366065	0.012	<1	4.70	4	417	<2	36	3.38	<4	10	10	18	2.16	0.03	9	1.63	1537	<1	28	516	35	0.77	<5	<5	<10	219	2018	2	41	<10	6	75
307872	1366066	0.020	<1	4.21	12	398	<2	9	2.16	<4	10	20	25	1.88	<0.01	12	1.30	968	<1	37	505	40	0.70	5	9	<10	182	1726	<2	38	<10	6	122
307873	1366067	0.078	1	3.84	21	409	<2	3	1.98	<4	9	17	36	1.77	0.08	11	1.14	873	<1	32	502	69	1.04	<5	<5	<10	156	1546	<2	37	<10	5	245
307874	1366068	0.044	<1	2.34	9	299	<2	<1	1.33	<4	9	13	27	1.56	0.03	10	0.95	690	<1	32	441	23	0.59	<5	<5	<10	123	1518	<2	34	<10	5	65
307875	1366069	0.312	1	2.77	38	319	<2	5	1.39	<4	6	13	24	1.32	<0.01	10	0.82	665	<1	32	313	95	0.75	<5	<5	<10	87	1162	<2	22	<10	4	312
307876	1366070	<0.005	<1	2.27	<2	291	<2	5	2.09	4	16	45	23	3.22	<0.01	7	1.31	649	<1	34	572	7	0.12	<5	8	<10	201	2540	<2	110	17	15	54
307877	1366071	0.008	6	3.62	26	342	<2	15	1.87	9	6	14	721	1.65	<0.01	11	0.84	831	<1	33	273	97	1.40	<5	<5	<10	59	1181	<2	21	33	4	2512
307878	1366072	0.043	1	3.64	28	377	<2	6	1.24	<4	7	12	40	1.43	<0.01	10	0.78	718	<1	29	294	206	0.99	<5	<5	<10	82	1206	<2	21	<10	4	334
307879	1366073	0.697	2	2.36	23	294	<2	13	0.25	<4	4	10	69	0.82	<0.01	2	0.36	213	<1	25	206	396	0.62	<5	5	<10	49	898	<2	16	<10	3	424

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Saturday, November 24, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 11/06/2012
 Date Completed: 11/16/2012
 Job #: 201244235
 Reference: TL12-278
 Sample #: 110

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
307880	1366074	0.034	1	3.64	16	420	<2	2	0.11	<4	4	10	63	0.83	<0.01	5	0.42	240	<1	25	312	277	0.58	<5	<5	<10	55	1131	<2	21	11	4	530
307881D	1366074	0.046	1	3.65	15	418	<2	<1	0.09	<4	4	11	54	0.80	0.02	5	0.41	234	<1	29	306	261	0.56	<5	<5	<10	56	1123	<2	21	10	4	508
307882	1366075	0.047	<1	3.20	12	403	<2	<1	<0.01	<4	4	6	21	0.67	<0.01	1	0.30	<100	<1	23	304	140	0.51	<5	6	<10	52	983	<2	19	<10	4	162
307883	1366076	0.021	1	3.36	16	394	<2	4	<0.01	<4	4	3	29	0.75	0.05	2	0.30	<100	<1	21	318	180	0.63	<5	<5	<10	53	970	<2	19	<10	4	99
307884	1366077	0.033	<1	3.63	9	350	<2	<1	<0.01	<4	4	6	11	0.58	<0.01	<1	0.26	<100	<1	21	283	52	0.40	<5	5	<10	59	843	<2	19	<10	4	126
307885	1366078	0.050	1	2.55	14	454	<2	<1	<0.01	<4	6	14	17	0.80	<0.01	2	0.28	<100	<1	27	257	109	0.68	<5	<5	<10	56	964	<2	23	<10	4	125
307886	1366079	0.017	<1	2.11	8	283	<2	<1	0.89	<4	6	10	11	0.49	<0.01	<1	0.24	135	<1	25	232	33	0.40	<5	<5	<10	125	1074	<2	28	<10	4	56
307887	1366080	2.027	<1	1.16	6	267	<2	<1	1.66	<4	14	35	25	3.00	<0.01	3	1.14	576	<1	32	500	10	0.09	<5	<5	<10	168	2051	<2	98	20	12	49
307888	1366081	0.018	<1	0.99	7	161	<2	5	2.25	<4	5	5	11	0.30	<0.01	<1	0.27	211	<1	17	<100	20	0.18	<5	7	<10	150	896	<2	22	<10	2	46
307889	1366082	0.017	<1	0.46	6	194	<2	<1	0.51	<4	6	6	10	0.27	<0.01	<1	0.19	<100	<1	20	207	21	0.20	<5	5	<10	86	997	<2	25	<10	3	62
307890	1366083	0.018	<1	0.82	5	209	<2	11	0.61	<4	6	4	18	0.31	<0.01	<1	0.16	118	<1	19	174	28	0.24	<5	<5	<10	102	987	<2	24	<10	3	23
307891	1366084	0.012	<1	2.41	13	322	<2	<1	0.49	<4	8	8	6	0.42	<0.01	3	0.24	238	<1	19	266	49	0.31	<5	<5	<10	84	1455	<2	31	<10	4	31
307892D	1366084	0.014	<1	3.59	15	423	<2	7	0.76	<4	8	10	7	0.46	<0.01	4	0.25	258	<1	27	298	50	0.35	<5	<5	<10	119	1570	<2	34	<10	4	33
307893	1366085	0.012	<1	2.53	11	321	<2	<1	0.90	<4	7	7	10	0.34	<0.01	1	0.23	148	<1	20	194	29	0.26	<5	<5	<10	132	1295	<2	29	<10	3	38
307894	1366086	0.024	<1	2.05	13	320	<2	3	0.59	<4	8	11	24	0.54	<0.01	4	0.36	183	<1	27	230	50	0.36	<5	<5	<10	105	1354	<2	29	<10	4	173
307895	1366087	0.021	<1	2.92	6	354	<2	<1	1.85	<4	11	15	40	1.73	<0.01	7	0.79	469	<1	33	439	37	0.85	<5	<5	<10	194	1671	<2	32	<10	6	79
307896	1366088	0.040	<1	3.29	3	424	<2	10	2.07	<4	9	15	19	1.60	<0.01	10	1.00	642	<1	26	464	177	0.74	<5	6	<10	191	1498	<2	32	<10	6	419
307897	1366089	0.151	1	2.24	22	334	<2	1	1.35	5	9	12	22	1.83	<0.01	10	0.94	711	<1	26	426	290	1.24	<5	<5	<10	91	1592	<2	30	19	5	1194
307898	1366090	0.010	<1	2.84	<2	313	<2	<1	2.18	<4	15	45	21	3.21	<0.01	8	1.34	636	<1	34	577	8	0.13	<5	<5	<10	217	2401	<2	111	21	15	53
307899	1366091	0.688	<1	4.33	21	518	<2	<1	2.06	<4	8	12	27	1.75	<0.01	13	1.19	762	<1	31	431	253	0.83	<5	<5	<10	131	1664	<2	31	12	6	357

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Saturday, November 24, 2012

Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 11/06/2012
 Date Completed: 11/16/2012
 Job #: 201244235
 Reference: TL12-278
 Sample #: 110

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
307900	1366092	0.214	4	3.19	21	419	<2	<1	1.27	9	12	10	91	2.10	<0.01	7	0.85	622	<1	30	427	899	1.70	<5	<5	<10	89	1543	<2	28	34	5	2417
307901	1366093	0.014	<1	2.43	<2	489	<2	<1	0.10	<4	3	5	4	0.87	<0.01	8	1.12	351	<1	18	236	77	0.26	<5	<5	<10	57	852	<2	14	<10	3	77
307902	1366094	0.036	<1	2.62	<2	452	<2	11	0.31	<4	3	14	5	0.79	<0.01	7	0.68	332	<1	24	227	17	0.35	<5	<5	<10	81	784	<2	14	<10	3	65
307903D	1366094	0.057	<1	2.85	<2	465	<2	<1	0.37	<4	4	16	8	0.82	<0.01	7	0.69	341	<1	27	242	18	0.35	<5	<5	<10	89	796	<2	15	<10	3	68
307904	1366095	0.073	<1	3.51	18	492	<2	<1	0.26	<4	4	7	5	0.97	<0.01	4	0.51	344	<1	24	231	34	0.78	<5	<5	<10	64	914	<2	15	<10	3	161
307905	1366096	0.151	<1	3.09	20	454	<2	<1	0.18	<4	4	6	5	0.92	<0.01	3	0.45	322	<1	22	216	31	0.78	<5	<5	<10	59	854	<2	14	<10	3	181
307906	1366097	0.123	<1	3.28	24	437	<2	<1	<0.01	4	4	6	3	1.10	<0.01	3	0.35	231	<1	22	206	40	1.10	<5	<5	<10	47	875	<2	14	11	3	630
307907	1366098	0.034	<1	3.19	17	474	<2	<1	0.44	<4	4	6	8	0.88	<0.01	6	0.59	479	<1	22	229	25	0.64	<5	<5	<10	72	926	<2	15	<10	3	61
307908	1366099	0.017	<1	2.37	5	399	<2	<1	0.60	<4	3	6	4	0.85	<0.01	5	0.92	647	<1	22	231	28	0.32	<5	<5	<10	75	911	<2	15	<10	3	56
307909	1366100	0.256	<1	<0.01	421	4616	<2	4	0.71	<4	6	10	29	2.79	0.03	<1	0.12	<100	<1	20	<100	19	0.29	11	<5	<10	61	343	<2	14	43	6	16
307910	1366101	0.065	<1	2.69	12	399	<2	3	1.45	<4	9	12	10	1.80	0.10	7	1.00	546	<1	28	443	30	0.47	<5	5	<10	134	1641	3	33	<10	6	50
307911	1366102	0.178	<1	2.55	9	314	<2	<1	1.49	<4	12	36	54	1.74	<0.01	13	1.01	485	<1	33	447	52	0.68	<5	<5	<10	71	1820	<2	40	<10	7	111
307912	1366103	0.040	<1	4.24	9	505	<2	<1	1.51	<4	12	16	29	1.58	0.04	11	0.86	387	<1	29	470	49	0.54	<5	<5	<10	154	2040	<2	41	<10	6	100
307913	1366104	0.042	<1	3.42	24	396	<2	<1	1.06	<4	12	15	13	1.10	<0.01	6	0.80	357	<1	31	493	38	0.71	<5	5	<10	90	1680	<2	39	<10	6	82
307914D	1366104	0.045	<1	3.82	22	419	<2	5	1.13	<4	13	15	21	1.14	<0.01	7	0.82	366	<1	37	498	38	0.74	<5	<5	<10	95	1761	<2	41	<10	6	95
307915	1366105	0.016	1	3.26	6	326	<2	3	0.78	<4	11	76	27	1.29	0.03	7	0.87	370	<1	57	766	54	0.49	<5	<5	<10	71	1809	<2	36	11	7	164
307916	1366106	0.012	<1	2.84	<2	386	<2	5	1.25	<4	6	7	12	1.39	<0.01	4	0.73	461	<1	25	581	35	0.53	<5	<5	<10	93	1528	<2	29	<10	5	45
307917	1366107	0.014	<1	3.06	10	472	<2	2	1.56	<4	7	27	14	1.60	<0.01	6	0.97	520	<1	35	679	43	0.64	<5	<5	<10	100	1691	<2	30	<10	6	69
307918	1366108	0.009	<1	2.76	<2	398	<2	2	1.47	<4	5	8	6	1.33	0.02	7	0.86	534	<1	22	527	27	0.51	<5	<5	<10	70	1533	<2	26	<10	5	137
307919	1366109	0.069	1	3.04	22	480	<2	<1	0.52	<4	6	8	16	1.43	<0.01	9	0.69	402	<1	24	485	307	1.06	<5	<5	<10	58	1509	<2	26	15	4	562

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Saturday, November 24, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 11/06/2012
 Date Completed: 11/16/2012
 Job #: 201244235
 Reference: TL12-278
 Sample #: 110

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
307920	1366110	0.006	<1	1.13	<2	251	<2	<1	1.80	<4	14	38	18	2.85	<0.01	3	1.16	562	<1	35	515	8	0.08	<5	<5	<10	173	2095	<2	99	16	13	48
307921	1366111	0.065	<1	2.69	24	469	<2	<1	0.50	<4	5	9	7	1.31	<0.01	7	0.64	380	<1	25	476	163	1.07	<5	<5	<10	46	1416	<2	24	11	4	384
307922	1366112	0.086	<1	2.70	21	428	<2	8	1.30	<4	4	7	6	1.26	0.02	7	0.98	631	<1	22	503	102	0.84	<5	<5	<10	77	1324	<2	22	<10	4	227
307923	1366113	2.105	2	1.79	51	316	<2	<1	0.57	10	5	11	72	2.50	<0.01	5	0.61	400	<1	27	429	337	2.55	<5	<5	<10	42	1269	<2	22	29	4	2197
307924	1366114	0.680	1	3.35	11	337	<2	1	1.26	<4	6	12	87	1.15	<0.01	9	1.33	1000	<1	24	506	58	0.36	<5	<5	<10	84	1485	<2	26	<10	5	173
307925R	1366114	0.572	2	3.34	10	333	<2	<1	1.18	<4	6	8	83	1.11	<0.01	8	1.26	929	<1	24	472	60	0.37	<5	7	<10	82	1434	<2	25	<10	5	158
307926	1366115	0.056	<1	2.92	8	266	<2	2	1.33	<4	10	7	4	1.00	<0.01	6	1.56	889	<1	25	421	38	0.25	<5	<5	<10	96	1192	<2	23	<10	4	98
307927	1366116	0.067	<1	3.37	11	286	<2	<1	1.43	<4	11	6	16	1.07	<0.01	7	1.64	950	<1	30	438	39	0.28	<5	<5	<10	100	1284	<2	24	<10	4	142
307928	1366117	0.038	<1	8.30	23	467	<2	9	1.70	<4	11	13	11	0.95	0.09	21	1.27	728	<1	31	494	42	0.51	5	<5	<10	143	1791	<2	30	<10	8	313
307929	1366118	0.061	1	8.60	22	594	<2	3	1.42	<4	9	20	16	1.15	0.13	25	0.99	590	<1	37	478	118	0.89	<5	<5	<10	136	1844	2	31	13	8	298
307930	1366119	2.304	37	2.05	26	372	<2	<1	0.53	9	9	8	382	1.66	<0.01	7	0.73	637	<1	32	407	2724	1.62	<5	<5	<10	77	1348	<2	23	34	4	2631
307931	1366120	4.807	63	0.31	35	314	<2	8	1.05	22	14	26	52	3.16	<0.01	1	0.80	486	<1	28	515	603	0.39	26	<5	229	144	1595	<2	89	56	11	1904
307932	1366121	0.677	8	1.61	13	306	<2	9	0.28	<4	8	12	39	1.01	<0.01	6	0.79	627	<1	30	446	154	0.59	<5	<5	<10	62	1350	<2	24	<10	4	127
307933	1366122	0.452	2	3.10	27	612	<2	<1	0.47	<4	5	17	59	1.42	<0.01	5	0.74	529	<1	30	404	223	1.21	<5	<5	<10	71	1468	<2	29	<10	4	258
307934	1366123	0.038	<1	0.96	24	160	<2	7	0.22	<4	6	4	8	1.12	<0.01	7	1.22	740	<1	25	362	33	0.67	<5	<5	<10	46	1239	<2	24	<10	4	61
307935	1366124	0.095	<1	1.74	22	203	<2	1	0.18	4	9	10	14	1.25	<0.01	5	0.73	373	<1	26	377	31	1.12	<5	<5	<10	49	1355	<2	25	10	4	673
307936D	1366124	0.051	<1	1.91	20	201	<2	<1	0.23	<4	8	10	10	1.20	<0.01	6	0.72	361	<1	28	371	31	1.06	<5	<5	<10	53	1345	<2	25	<10	4	69
307937	1366125	0.125	<1	2.03	19	213	<2	10	0.32	<4	5	7	8	0.77	<0.01	2	0.71	338	<1	22	323	119	0.62	<5	<5	<10	50	1099	<2	20	<10	3	85
307938	1366126	0.667	4	1.06	57	155	<2	<1	<0.01	6	4	6	37	1.23	<0.01	<1	0.26	<100	<1	23	288	567	1.38	<5	<5	<10	31	818	<2	16	21	3	1394
307939	1366127	0.033	1	1.30	26	188	<2	1	0.64	<4	6	8	13	1.51	<0.01	3	0.96	494	<1	24	373	34	1.36	<5	<5	<10	51	1145	<2	21	<10	3	79

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Saturday, November 24, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 11/06/2012
 Date Completed: 11/16/2012
 Job #: 201244235
 Reference: TL12-278
 Sample #: 110

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
307940	1366128	0.020	<1	1.51	18	170	<2	8	0.50	<4	7	7	8	1.51	<0.01	4	0.80	407	<1	26	382	29	1.35	<5	<5	<10	53	1337	2	25	<10	4	62
307941	1366129	0.057	<1	1.59	66	170	<2	<1	0.75	<4	7	15	20	1.57	<0.01	6	0.92	598	<1	28	420	30	1.12	<5	<5	<10	62	1430	<2	29	<10	5	62
307942	1366130	0.008	<1	0.82	<2	238	<2	<1	1.91	<4	16	41	24	3.22	<0.01	4	1.28	639	<1	37	566	9	0.09	<5	<5	<10	160	2341	<2	110	15	14	80
307943	1366131	0.014	<1	1.13	25	158	<2	1	0.36	<4	7	11	6	1.39	<0.01	3	0.72	487	<1	31	396	29	1.10	<5	<5	<10	44	1322	<2	25	<10	4	70
307944	1366132	0.022	<1	2.38	23	158	<2	<1	1.25	<4	8	11	7	1.45	<0.01	5	1.01	707	<1	33	344	38	1.08	<5	<5	<10	73	1208	2	22	<10	4	207
307945	1366133	0.160	2	2.81	26	193	<2	7	1.72	9	5	9	69	2.12	<0.01	8	1.22	568	<1	26	359	1179	1.65	<5	<5	<10	61	1264	<2	23	38	4	2780
307946	1366134	0.084	<1	3.27	16	450	<2	9	1.66	<4	5	14	31	1.33	<0.01	10	1.58	742	<1	30	319	139	0.58	<5	7	<10	74	1273	<2	21	11	4	553
307947D	1366134	0.079	<1	2.74	18	421	<2	5	1.62	<4	5	14	31	1.33	<0.01	9	1.58	750	<1	28	314	136	0.56	<5	9	<10	69	1247	<2	21	12	4	552
307948	1366135	0.065	<1	2.40	18	405	<2	9	0.95	<4	5	9	11	1.14	0.03	12	1.04	436	<1	23	308	59	0.64	<5	<5	<10	51	1254	<2	20	<10	4	114
307949	1366136	0.072	<1	1.53	20	358	<2	<1	0.98	<4	5	11	15	1.11	0.02	10	1.05	450	<1	27	315	60	0.61	<5	<5	<10	39	1157	<2	18	<10	3	136
307950	1366137	0.119	1	1.56	26	340	<2	1	0.57	<4	5	17	105	1.14	0.04	3	0.55	234	<1	34	286	219	0.81	<5	<5	<10	27	1029	<2	18	<10	3	271
307951	1366138	0.100	<1	2.35	30	360	<2	4	0.20	<4	6	15	7	1.10	<0.01	2	0.55	148	<1	30	411	47	0.96	<5	<5	<10	31	1053	<2	21	<10	3	39
307952	1366139	0.165	<1	2.17	29	355	<2	<1	<0.01	<4	5	8	16	0.80	<0.01	<1	0.29	<100	<1	24	511	41	0.75	<5	<5	<10	31	835	<2	18	<10	4	50
307953	1366140	1.917	<1	0.33	6	224	<2	<1	1.71	<4	16	41	29	3.55	<0.01	4	1.27	662	<1	36	573	13	0.08	<5	<5	<10	131	2260	<2	111	14	14	60
307954	1366141	0.081	<1	2.23	20	333	<2	3	<0.01	<4	5	8	11	0.91	<0.01	<1	0.28	<100	<1	25	540	48	0.87	<5	<5	<10	35	766	<2	19	<10	3	55
307955	1366142	0.139	<1	2.29	22	401	<2	<1	<0.01	<4	6	5	5	1.23	<0.01	<1	0.38	<100	<1	23	635	71	1.22	<5	<5	<10	34	908	<2	20	11	4	425
307956	1366143	2.438	6	3.61	59	348	<2	2	1.17	9	6	9	452	2.50	<0.01	22	2.41	617	<1	23	401	1534	2.16	<5	<5	<10	62	884	<2	22	31	3	2254
307957	1366144	0.075	<1	3.19	19	409	<2	<1	1.31	<4	5	12	24	1.55	<0.01	13	1.87	443	<1	20	361	111	0.89	<5	5	<10	56	976	<2	23	<10	3	125
307958D	1366144	0.069	<1	3.39	21	420	<2	4	1.32	<4	6	14	25	1.58	<0.01	13	1.84	439	<1	27	368	108	0.92	<5	<5	<10	58	1005	3	23	<10	3	124
307959	1366145	0.055	<1	2.47	18	348	<2	<1	0.36	<4	11	54	48	1.80	<0.01	8	1.08	261	<1	49	418	115	1.00	<5	7	<10	35	1140	<2	42	<10	7	158

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By:  Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Saturday, November 24, 2012

Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 11/06/2012
 Date Completed: 11/16/2012
 Job #: 201244235
 Reference: TL12-278
 Sample #: 110

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
307960	1366146	1.538	9	1.96	64	292	<2	<1	0.28	16	14	97	125	2.80	<0.01	2	0.63	181	<1	69	588	1954	2.73	6	<5	<10	33	1079	<2	60	61	10	4464
307961	1366147	0.157	1	2.96	25	265	<2	4	1.04	<4	19	119	44	3.25	<0.01	16	1.84	551	<1	75	507	102	1.09	<5	<5	<10	46	1714	<2	73	<10	11	150
307962	1366148	0.054	1	2.01	9	205	<2	6	0.80	<4	20	112	54	3.50	<0.01	23	2.28	552	<1	78	479	58	0.49	<5	<5	<10	40	1950	<2	79	<10	10	134
307963	1366149	0.336	2	3.51	32	284	<2	14	0.17	4	25	118	104	3.98	<0.01	18	1.79	446	<1	95	528	118	1.86	<5	<5	<10	42	1607	<2	92	<10	11	235
307964	1366150	<0.005	<1	3.46	<2	339	<2	12	2.24	<4	16	45	21	3.24	<0.01	8	1.35	652	<1	36	585	10	0.13	<5	<5	<10	236	2606	<2	112	24	15	50
307965	1366151	1.359	16	2.68	101	338	2	14	<0.01	<4	8	20	36	1.25	<0.01	<1	0.35	<100	<1	28	436	549	1.20	6	<5	<10	35	862	<2	28	13	4	816
307966	1366152	0.408	2	2.94	28	456	<2	<1	0.03	<4	6	12	15	1.08	<0.01	1	0.54	143	<1	32	420	111	0.87	<5	<5	<10	34	1014	<2	21	<10	4	277
307967	1366153	0.054	<1	3.55	17	477	<2	5	0.68	<4	6	9	18	1.08	<0.01	4	0.86	232	<1	29	411	65	0.61	<5	<5	<10	41	1187	<2	22	<10	4	116
307968	1366154	0.018	<1	3.87	18	441	<2	<1	1.49	<4	6	7	11	1.31	<0.01	12	1.73	418	<1	32	320	69	0.53	<5	<5	<10	69	1292	<2	23	<10	4	85
307969D	1366154	0.021	<1	4.08	18	457	<2	<1	1.50	<4	6	9	11	1.31	<0.01	13	1.74	421	<1	35	325	68	0.53	<5	<5	<10	68	1332	<2	24	<10	4	86
307970	1366155	1.723	28	2.55	51	376	<2	7	0.55	<4	6	11	55	1.18	<0.01	5	0.86	226	<1	38	274	471	0.81	13	<5	<10	39	1142	<2	22	10	3	359
307971	1366156	1.183	19	1.89	44	336	<2	<1	0.42	<4	7	10	38	1.13	<0.01	3	0.77	192	<1	30	268	479	0.83	7	5	<10	33	1045	<2	20	<10	3	303
307972	1366157	1.548	65	1.69	122	311	<2	9	<0.01	14	5	7	108	1.35	<0.01	<1	0.27	<100	<1	26	206	3524	1.65	29	<5	<10	28	906	<2	16	54	3	4511
307973	1366158	0.162	4	3.51	37	424	<2	3	0.81	<4	6	10	13	1.19	<0.01	3	0.99	243	<1	34	369	184	0.91	<5	7	<10	59	1141	<2	21	<10	4	187
307974	1366159	0.455	2	<0.01	38	238	<2	<1	<0.01	<4	4	<1	9	0.66	<0.01	<1	0.25	<100	<1	16	213	120	0.63	<5	<5	<10	20	609	<2	12	<10	2	106
307975	1366160	0.238	<1	<0.01	405	>5000	<2	6	0.63	<4	5	9	35	2.66	<0.01	<1	0.11	<100	<1	20	<100	26	0.41	13	<5	<10	88	265	<2	13	35	5	22
307976	1366169	0.068	<1	4.24	16	467	2	9	2.11	<4	10	10	35	2.01	<0.01	9	1.48	449	<1	29	499	49	0.50	<5	6	<10	80	1705	<2	34	<10	5	172
307977	1366170	<0.005	<1	0.96	3	222	<2	<1	1.72	<4	14	36	20	2.84	<0.01	3	1.16	563	<1	34	504	11	0.09	<5	<5	<10	151	2098	<2	97	15	13	45
307978	1366171	0.288	1	2.58	28	295	<2	<1	1.80	5	8	7	8	1.72	<0.01	5	1.05	522	<1	26	455	148	0.96	<5	<5	<10	62	1458	<2	29	15	4	937
307979	1366172	1.047	2	2.19	43	226	<2	<1	1.10	7	8	14	65	2.64	<0.01	10	0.84	322	<1	30	405	214	2.03	<5	<5	<10	82	1358	2	32	22	5	1465

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Saturday, November 24, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 11/06/2012
 Date Completed: 11/16/2012
 Job #: 201244240
 Reference: TL12-278
 Sample #: 8

Acc #	Client ID	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
308131	1366161	1	>10.00	47	826	<2	<1	0.16	<4	7	184	11	1.10	1.17	10	<0.01	<100	<1	12	417	78	0.99	<5	10	<10	39	990	<2	21	<10	4	51
308132	1366162	3	>10.00	78	782	<2	3	0.38	<4	11	329	63	1.81	1.23	22	<0.01	<100	<1	38	687	148	1.83	11	5	<10	47	1212	4	57	<10	9	116
308133	1366163	91	>10.00	388	851	<2	13	1.80	<4	11	306	536	1.90	1.38	30	0.18	201	<1	29	605	1872	1.75	92	<5	<10	50	1220	4	49	<10	8	113
308134	1366164	1	>10.00	16	557	<2	10	1.11	<4	<1	58	15	0.08	1.32	27	<0.01	<100	<1	7	<100	13	0.27	<5	<5	<10	54	231	9	3	<10	6	109
308135	1366165	12	>10.00	50	1105	<2	4	0.80	<4	9	207	64	1.50	1.25	33	<0.01	<100	2	22	486	492	1.61	21	<5	<10	96	1469	2	36	18	10	914
308136	1366166	11	>10.00	65	1243	<2	3	0.35	<4	8	227	108	1.48	1.16	18	<0.01	<100	<1	17	479	574	1.49	24	<5	<10	62	1316	7	33	18	7	892
308137	1366167	56	9.17	90	888	<2	<1	0.72	8	6	275	227	1.93	1.21	15	<0.01	<100	2	15	561	2603	2.17	71	<5	<10	48	916	5	23	33	7	2407
308138	1366168	5	>10.00	55	1056	<2	14	1.82	<4	10	198	36	1.79	1.20	36	0.33	255	<1	17	634	301	1.33	7	<5	<10	50	1754	8	34	17	7	793

PROCEDURE CODES: ALP1, ALMA1, AISu1, ALPM1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, December 3, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 11/19/2012
 Date Completed: 11/30/2012
 Job #: 201244373
 Reference: TL 12 279
 Sample #: 165

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
318152	1366280	2.120	<1	2.73	6	317	<2	17	2.01	<4	14	48	31	3.29	<0.01	9	1.22	632	<1	37	545	11	0.10	<5	<5	<10	183	2170	<2	107	20	14	60
318153	1366281	<0.005	<1	<0.01	4	314	2	13	1.07	<4	8	15	9	1.74	<0.01	5	0.58	319	<1	31	422	11	0.87	<5	<5	<10	88	1489	<2	34	<10	4	66
318154	1366282	0.010	<1	1.95	9	287	<2	10	1.44	<4	8	26	10	1.70	<0.01	9	0.54	316	<1	49	429	10	0.74	<5	<5	<10	187	1607	<2	43	<10	5	61
318155	1366283	0.008	<1	2.55	3	352	<2	12	1.55	<4	7	22	8	1.67	<0.01	11	0.51	401	<1	44	406	11	0.84	<5	<5	<10	207	1646	<2	42	<10	5	101
318156	1366284	0.005	<1	6.71	13	507	2	18	2.18	<4	7	25	15	1.81	<0.01	14	0.53	533	<1	48	441	16	0.93	5	<5	<10	401	1831	<2	49	<10	6	238
318157	1366285	0.005	2	6.50	15	498	<2	4	2.51	<4	5	18	17	1.41	0.11	20	0.27	528	<1	33	317	16	1.18	<5	<5	<10	436	1386	<2	36	<10	6	230
318158	1366286	<0.005	<1	6.06	<2	481	2	14	2.06	<4	7	21	6	1.55	0.18	10	0.48	282	<1	36	392	8	0.33	<5	<5	<10	533	1710	<2	42	<10	6	61
318159	1366287	0.011	1	6.63	12	425	<2	21	2.03	<4	7	23	6	1.61	0.13	16	0.58	387	<1	36	402	17	0.63	<5	<5	<10	372	1940	<2	45	<10	5	49
318160	1366288	0.014	<1	3.82	13	380	2	19	1.81	<4	7	29	13	1.70	0.02	9	0.58	341	<1	56	403	11	0.61	<5	<5	<10	387	1715	<2	47	18	5	38
318161	1366289	0.005	<1	5.24	7	567	2	20	1.86	<4	7	29	8	1.58	0.26	15	0.43	317	<1	49	399	11	0.58	<5	<5	<10	459	1883	<2	49	<10	5	34
318162D	1366289	0.007	<1	4.37	4	456	<2	12	1.69	<4	7	31	8	1.53	0.15	9	0.51	302	<1	50	408	11	0.46	<5	<5	<10	406	1689	<2	46	<10	5	31
318163	1366290	0.005	<1	4.91	8	380	<2	10	2.32	<4	14	48	20	2.99	0.23	11	1.17	598	<1	33	514	12	0.15	<5	<5	<10	245	2375	<2	106	22	15	50
318164	1366291	0.022	1	6.49	15	616	2	13	2.12	<4	7	24	13	1.59	<0.01	16	0.53	619	<1	34	391	62	0.85	<5	<5	<10	390	1760	<2	43	<10	6	126
318165	1366292	0.018	2	5.63	16	544	2	23	1.56	<4	8	24	10	1.62	<0.01	25	0.55	543	<1	36	415	37	1.02	<5	<5	<10	255	1774	<2	47	<10	5	88
318166	1366293	0.043	<1	6.21	24	520	<2	10	1.85	<4	8	23	12	1.71	<0.01	18	0.56	483	<1	35	441	25	0.83	<5	<5	<10	267	1672	<2	46	10	5	86
318167	1366294	0.013	<1	0.79	5	185	<2	30	1.73	<4	7	19	5	1.50	<0.01	8	0.58	375	<1	33	408	7	0.43	<5	<5	<10	52	1492	<2	44	<10	4	15
318168	1366295	0.016	<1	5.12	4	621	<2	7	1.55	<4	7	17	7	1.77	<0.01	13	0.68	414	<1	31	483	16	0.50	<5	<5	<10	277	1781	<2	43	<10	5	51
318169	1366296	0.017	<1	3.21	5	520	<2	14	1.40	<4	7	16	8	1.75	<0.01	10	0.67	402	<1	33	446	12	0.45	<5	<5	<10	219	1634	<2	42	<10	5	41
318170	1366297	0.015	<1	5.30	5	545	<2	5	2.35	<4	9	23	13	2.15	0.07	14	0.85	488	<1	35	483	21	0.56	<5	<5	<10	327	1849	<2	49	<10	6	86
318171	1366298	0.023	<1	5.60	18	408	<2	15	1.32	<4	4	19	21	1.12	0.12	14	0.66	602	<1	36	262	82	0.50	<5	<5	<10	91	1182	<2	29	<10	4	251

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, December 3, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 11/19/2012
 Date Completed: 11/30/2012
 Job #: 201244373
 Reference: TL 12 279
 Sample #: 165

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
318172	1366299	0.034	<1	6.07	28	468	2	24	1.44	<4	4	31	9	1.17	0.19	17	0.61	591	<1	55	262	112	0.72	<5	<5	<10	91	1214	<2	36	<10	4	201
318173D	1366299	0.032	<1	6.43	23	488	<2	6	1.49	<4	5	31	9	1.20	0.10	18	0.63	612	<1	57	265	113	0.76	<5	<5	<10	93	1262	<2	36	<10	5	200
318174	1366300	5.213	63	4.53	37	442	<2	7	1.39	19	12	31	45	2.59	0.27	10	0.68	441	<1	28	460	540	0.46	65	<5	223	200	1744	<2	78	58	12	1698
318175	1366301	0.057	1	5.30	19	453	2	8	0.57	<4	4	21	37	1.07	0.18	11	0.33	256	<1	36	249	353	0.90	<5	<5	<10	79	1172	<2	28	10	4	306
318176	1366302	0.028	1	4.32	20	491	2	14	0.34	<4	4	20	12	0.84	<0.01	14	0.12	<100	<1	34	202	50	0.88	<5	<5	<10	79	1299	<2	31	<10	3	92
318177	1366303	0.025	<1	4.25	13	416	2	17	0.91	<4	8	16	18	0.62	<0.01	10	0.15	119	<1	34	103	29	0.62	<5	<5	<10	134	1138	<2	35	<10	3	58
318178	1366304	0.021	6	2.32	20	199	2	3	2.98	<4	17	222	39	1.51	<0.01	4	1.33	348	<1	161	1337	23	0.73	<5	<5	<10	180	1851	<2	48	<10	11	50
318179	1366305	0.020	<1	2.62	<2	315	<2	16	0.55	<4	5	16	11	0.30	<0.01	5	0.12	<100	<1	27	228	11	0.22	<5	<5	<10	77	1080	<2	31	<10	3	64
318180	1366306	0.018	1	5.66	10	372	<2	10	1.38	<4	5	21	10	0.33	<0.01	6	0.11	108	<1	39	189	21	0.27	<5	<5	<10	158	1251	<2	37	<10	4	66
318181	1366307	0.063	<1	4.48	11	341	<2	11	1.49	<4	5	26	10	0.40	<0.01	4	0.15	166	<1	50	260	14	0.24	<5	<5	<10	122	1317	<2	41	<10	4	34
318182	1366308	0.017	<1	4.67	19	377	<2	8	1.05	<4	6	15	7	0.31	<0.01	5	0.11	101	<1	27	300	19	0.24	<5	<5	<10	137	1275	<2	32	<10	4	17
318183	1366309	0.021	<1	5.20	<2	422	<2	23	1.45	<4	4	19	8	0.30	0.18	12	0.07	134	<1	29	226	12	0.38	<5	<5	10	194	1248	<2	36	<10	3	24
318184D	1366309	0.013	1	5.21	<2	423	2	23	1.45	<4	4	20	8	0.31	0.18	13	0.07	137	<1	32	227	12	0.38	<5	<5	<10	195	1260	<2	37	<10	4	26
318185	1366310	<0.005	1	5.54	5	451	2	14	2.26	<4	14	49	19	2.85	0.27	19	0.79	603	<1	28	491	10	0.33	<5	<5	<10	232	2920	<2	106	22	10	47
318186	1366311	0.013	<1	1.57	7	210	<2	16	0.57	<4	5	23	5	0.34	<0.01	2	0.11	100	<1	41	134	17	0.16	<5	<5	<10	95	1027	<2	31	<10	3	55
318187	1366312	0.016	<1	5.35	16	459	<2	10	2.05	<4	8	30	16	1.63	<0.01	14	0.60	438	<1	55	401	71	0.74	<5	<5	<10	238	1617	<2	45	<10	6	162
318188	1366313	0.017	<1	3.91	11	410	<2	11	1.32	<4	7	21	12	1.53	<0.01	13	0.64	351	<1	36	383	20	0.52	<5	<5	<10	138	1490	<2	38	<10	5	68
318189	1366314	0.046	<1	3.04	22	323	<2	10	1.22	<4	8	20	12	1.53	<0.01	16	0.76	477	<1	29	406	52	0.80	<5	<5	<10	72	1560	<2	29	<10	5	112
318190	1366315	0.529	3	3.23	32	355	<2	7	0.29	<4	6	15	59	1.30	<0.01	10	0.35	202	<1	27	328	523	1.28	<5	<5	<10	49	1316	<2	24	10	5	629
318191	1366316	0.725	3	2.38	27	287	2	16	0.22	4	7	13	93	1.32	<0.01	8	0.31	191	<1	26	315	490	1.34	<5	<5	<10	42	1159	<2	21	<10	4	724

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, December 3, 2012

Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 11/19/2012
 Date Completed: 11/30/2012
 Job #: 201244373
 Reference: TL 12 279
 Sample #: 165

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
318192	1366317	1.133	2	4.70	49	456	2	10	1.17	<4	6	19	29	1.50	<0.01	16	0.72	544	<1	34	371	459	1.02	<5	<5	<10	77	1574	<2	31	13	6	708
318193	1366318	0.067	<1	3.33	20	361	2	9	1.89	<4	6	17	10	1.45	<0.01	14	1.00	761	<1	30	384	55	0.55	<5	<5	<10	60	1522	<2	27	<10	5	77
318194	1366319	0.043	<1	5.29	26	441	<2	18	1.98	<4	8	17	10	1.59	<0.01	19	1.04	750	<1	31	432	29	0.65	<5	<5	<10	73	1718	<2	32	<10	5	61
318195D	1366319	0.047	<1	4.37	18	373	<2	14	1.93	<4	8	18	11	1.59	<0.01	17	1.05	749	<1	34	433	27	0.64	<5	<5	<10	66	1634	<2	31	<10	5	61
318196	1366320	0.257	<1	<0.01	367	>5000	<2	3	0.81	<4	5	15	27	2.57	<0.01	1	0.04	<100	<1	13	<100	18	0.39	15	<5	<10	70	552	<2	13	42	6	20
318197	1366321	0.044	<1	4.14	11	442	<2	13	2.14	<4	7	17	11	1.59	<0.01	12	1.02	763	<1	35	387	37	0.54	<5	<5	<10	87	1510	<2	26	<10	5	68
318198	1366322	0.269	<1	4.47	16	544	<2	22	1.73	<4	6	16	106	1.38	<0.01	12	0.80	623	<1	27	356	104	0.66	<5	<5	<10	79	1472	<2	26	<10	5	183
318199	1366323	0.107	<1	3.46	4	444	<2	13	1.59	<4	6	16	33	1.30	<0.01	9	0.76	581	<1	29	345	152	0.61	<5	<5	<10	75	1307	<2	23	<10	4	356
318200	1366324	0.026	2	2.24	9	326	<2	18	0.58	<4	3	17	5	0.94	<0.01	13	0.78	419	<1	33	172	417	0.41	<5	<5	<10	59	821	<2	14	10	3	568
318201	1366325	<0.005	<1	3.64	9	404	<2	16	0.86	<4	3	18	6	0.84	<0.01	14	0.78	402	<1	33	227	25	0.21	<5	<5	<10	72	921	<2	15	<10	3	66
318202	1366326	<0.005	<1	1.59	2	356	<2	12	0.17	<4	2	14	9	0.80	0.28	7	0.47	308	<1	29	200	9	0.24	<5	<5	<10	34	772	<2	12	<10	3	31
318203	1366327	0.007	<1	4.07	11	422	<2	17	0.94	<4	3	13	6	0.92	<0.01	10	0.64	466	<1	27	200	10	0.24	<5	<5	<10	88	906	<2	15	<10	3	40
318204	1366328	0.105	<1	4.57	31	456	<2	7	0.22	<4	3	18	5	0.98	0.18	8	0.31	194	<1	32	221	34	0.76	<5	<5	<10	49	811	<2	15	<10	3	331
318205	1366329	0.092	<1	4.75	21	459	<2	14	0.19	<4	3	22	4	0.99	<0.01	7	0.31	224	<1	38	182	31	0.88	<5	<5	<10	42	835	<2	15	<10	3	250
318206D	1366329	0.093	<1	3.02	9	366	<2	4	0.07	<4	2	20	3	0.95	<0.01	4	0.29	203	<1	32	172	27	0.85	<5	<5	<10	31	660	<2	12	<10	2	246
318207	1366330	<0.005	<1	4.14	11	340	<2	5	2.16	<4	14	46	19	2.91	0.07	9	1.13	573	<1	31	515	13	0.14	<5	6	<10	218	2154	<2	100	17	14	53
318208	1366331	0.023	<1	2.39	18	310	<2	14	0.24	<4	3	13	3	0.86	<0.01	4	0.39	279	<1	27	183	16	0.69	<5	<5	<10	46	622	<2	11	<10	2	45
318209	1366332	0.030	<1	3.89	21	358	<2	18	0.89	<4	3	13	4	1.00	0.08	10	0.70	655	<1	27	204	16	0.57	<5	<5	<10	94	864	<2	14	<10	3	109
318210	1366333	0.011	<1	1.76	7	351	<2	12	0.27	<4	3	14	5	0.82	<0.01	11	0.62	1114	<1	27	184	23	0.36	<5	<5	<10	39	816	<2	13	<10	2	44
318211	1366334	0.011	<1	4.22	10	410	<2	10	0.80	<4	3	11	11	0.90	<0.01	14	0.97	1175	<1	19	193	51	0.38	<5	<5	<10	79	892	<2	14	<10	3	303

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, December 3, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 11/19/2012
 Date Completed: 11/30/2012
 Job #: 201244373
 Reference: TL 12 279
 Sample #: 165

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
318212	1366335	0.136	1	4.83	8	348	2	13	1.52	<4	15	97	43	2.73	<0.01	14	1.12	554	<1	59	341	36	0.83	<5	<5	<10	131	1709	<2	58	<10	10	80
318213	1366336	0.082	1	5.62	14	349	<2	14	1.75	<4	16	107	39	2.90	<0.01	16	1.20	576	<1	70	375	41	0.86	<5	<5	<10	150	1879	<2	65	<10	11	75
318214	1366337	0.023	<1	6.25	45	585	2	21	0.58	<4	7	16	2	2.98	0.15	20	0.40	109	<1	27	129	33	3.14	<5	<5	<10	112	1369	<2	28	<10	4	36
318215	1366338	0.015	<1	7.19	19	675	<2	20	0.80	<4	7	15	5	0.78	0.17	22	0.45	121	<1	26	247	51	0.56	<5	<5	<10	148	1526	<2	30	<10	4	207
318216	1366339	0.102	1	5.45	21	386	<2	17	2.07	<4	8	26	16	1.68	<0.01	15	1.20	615	<1	39	382	51	0.53	<5	<5	<10	137	1583	<2	33	<10	6	163
318217R	1366339	0.086	1	3.02	13	389	<2	11	1.93	<4	7	24	14	1.61	0.03	16	0.93	607	<1	33	338	58	0.58	<5	<5	<10	136	1579	<2	33	<10	4	205
318218	1366340	1.769	<1	6.26	20	417	<2	19	2.34	<4	15	53	29	3.31	0.50	14	1.25	647	<1	36	571	13	0.23	<5	<5	<10	223	2619	<2	110	27	18	62
318219	1366341	0.081	1	3.39	8	304	<2	18	1.76	<4	7	25	16	1.60	<0.01	14	0.91	605	<1	33	313	93	0.57	<5	<5	<10	116	1390	<2	29	<10	4	160
318220	1366342	0.053	<1	1.75	26	309	<2	11	0.61	<4	7	21	10	1.27	<0.01	8	0.23	272	<1	32	308	22	1.07	<5	<5	<10	51	1376	<2	27	<10	3	49
318221	1366343	0.015	1	7.03	10	504	2	22	1.67	<4	8	26	14	1.43	0.63	21	0.71	569	<1	34	528	28	0.90	<5	<5	<10	96	2093	<2	38	<10	7	54
318222	1366344	0.011	1	4.54	11	465	2	26	1.83	<4	7	29	14	1.31	0.46	15	0.67	506	<1	40	528	37	0.62	<5	<5	<10	84	1771	<2	31	<10	5	63
318223	1366345	0.032	<1	3.55	2	393	<2	5	1.26	<4	5	11	15	1.41	0.29	9	0.66	463	<1	23	425	41	0.72	<5	<5	<10	74	1258	<2	23	<10	5	140
318224	1366346	0.042	1	2.72	10	467	<2	15	1.90	<4	4	19	7	1.34	<0.01	14	0.84	626	<1	33	401	299	0.76	<5	<5	<10	36	1332	<2	24	<10	4	564
318225	1366347	0.038	<1	2.54	28	447	<2	9	1.06	<4	3	11	4	1.00	<0.01	9	0.63	467	<1	22	364	28	0.59	<5	<5	<10	48	1185	<2	19	<10	4	55
318226	1366348	0.018	<1	1.58	8	197	<2	11	1.23	<4	3	14	4	0.90	<0.01	8	0.64	475	<1	22	345	18	0.43	<5	<5	<10	31	899	<2	15	<10	3	54
318227	1366349	0.248	<1	3.01	18	373	<2	9	1.34	<4	4	12	24	1.33	<0.01	9	0.68	555	<1	25	422	65	0.83	<5	<5	<10	58	1251	<2	20	<10	4	298
318228D	1366349	0.206	<1	2.04	28	233	<2	4	1.24	<4	4	16	24	1.33	0.01	8	0.68	553	<1	24	422	71	0.81	<5	<5	<10	43	1037	<2	17	<10	4	305
318229	1366350	<0.005	<1	1.64	19	194	<2	14	1.68	<4	13	44	20	2.75	<0.01	8	1.08	531	<1	35	497	5	0.13	<5	<5	<10	110	1901	<2	92	16	12	51
318230	1366351	0.065	<1	3.14	16	326	<2	8	1.37	<4	4	18	14	1.25	<0.01	11	0.78	649	<1	29	468	28	0.61	<5	<5	<10	53	1292	<2	22	<10	4	45
318231	1366352	0.628	4	2.54	27	299	<2	8	0.76	7	3	19	45	1.42	<0.01	6	0.60	456	<1	39	418	337	1.07	<5	<5	<10	37	1039	<2	18	19	4	1389

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, December 3, 2012

Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 11/19/2012
 Date Completed: 11/30/2012
 Job #: 201244373
 Reference: TL 12 279
 Sample #: 165

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
318232	1366353	0.162	<1	2.69	25	355	<2	10	0.70	<4	4	20	7	1.01	<0.01	7	0.62	447	<1	36	433	54	0.64	<5	<5	<10	46	1216	<2	21	<10	4	92
318233	1366354	0.187	<1	2.03	19	328	<2	8	0.23	<4	3	17	5	0.73	<0.01	4	0.30	189	<1	26	397	23	0.62	<5	<5	<10	30	994	<2	18	<10	3	49
318234	1366355	0.196	<1	1.52	17	317	<2	9	0.46	<4	6	19	6	0.78	<0.01	5	0.45	365	<1	27	318	28	0.59	<5	<5	<10	43	1006	<2	18	<10	3	50
318235	1366356	0.169	<1	1.99	23	281	<2	10	0.42	<4	5	15	8	0.81	0.09	4	0.57	387	<1	32	381	30	0.59	<5	<5	<10	36	939	<2	17	<10	4	77
318236	1366357	0.479	1	4.76	28	292	<2	17	0.56	<4	11	18	89	0.99	0.06	8	0.64	429	<1	36	419	143	0.73	<5	<5	<10	61	1299	<2	21	<10	6	344
318237	1366358	0.265	2	1.12	31	202	<2	15	0.20	<4	11	17	124	0.96	0.29	5	0.45	345	<1	40	382	65	0.77	<5	<5	<10	25	1067	<2	19	<10	4	120
318238	1366359	0.040	<1	1.57	18	271	<2	23	0.43	<4	6	14	5	0.87	<0.01	7	0.53	491	<1	34	316	19	0.53	<5	<5	<10	56	1128	<2	22	<10	3	33
318239D	1366359	0.036	<1	0.84	18	208	<2	32	0.25	<4	8	17	6	0.91	<0.01	5	0.60	504	<1	40	344	19	0.53	<5	<5	<10	32	1041	<2	20	<10	4	35
318240	1366360	5.226	64	1.99	31	318	<2	17	1.17	20	13	33	46	2.58	0.19	7	0.72	448	<1	29	467	576	0.44	24	<5	245	126	1594	<2	75	55	12	1808
318241	1366361	0.035	<1	1.48	19	205	<2	3	0.52	<4	4	16	5	0.85	<0.01	7	0.50	328	<1	31	318	16	0.53	<5	<5	<10	52	1056	<2	20	<10	3	13
318242	1366362	0.022	<1	1.27	26	280	<2	16	0.38	<4	7	18	4	0.95	<0.01	6	0.46	284	<1	40	343	14	0.65	<5	<5	<10	38	1131	<2	20	<10	3	31
318243	1366363	0.013	<1	1.79	18	250	<2	15	0.48	<4	5	17	4	0.91	<0.01	6	0.40	332	<1	37	334	19	0.58	<5	<5	<10	69	1167	<2	20	<10	3	68
318244	1366364	1.102	<1	1.64	15	263	<2	4	0.69	<4	8	21	11	1.30	<0.01	7	0.73	715	<1	35	357	17	0.48	<5	<5	<10	66	1337	<2	26	<10	4	58
318245	1366365	1.148	<1	2.31	10	295	<2	9	0.42	<4	7	22	15	1.53	<0.01	8	0.55	564	<1	38	370	15	0.62	<5	<5	<10	69	1267	<2	26	<10	4	44
318246	1366366	0.450	<1	1.60	23	269	<2	19	0.35	<4	6	27	21	1.32	<0.01	7	0.56	555	<1	34	363	29	0.65	<5	<5	<10	36	1186	<2	24	<10	4	47
318247	1366367	0.154	<1	3.14	4	339	<2	15	0.71	<4	8	28	35	1.85	<0.01	11	0.83	679	<1	36	416	21	0.60	<5	<5	<10	67	1673	<2	31	<10	5	85
318248	1366368	0.045	<1	0.52	6	140	<2	12	0.44	<4	5	23	6	1.42	<0.01	11	0.85	552	<1	35	327	29	0.39	<5	<5	<10	21	1184	<2	22	<10	4	439
318249	1366369	0.063	<1	1.96	12	194	<2	13	0.51	<4	6	18	12	1.34	<0.01	13	0.83	610	<1	34	365	30	0.41	<5	<5	<10	43	1242	<2	23	<10	4	41
318250D	1366369	0.051	<1	1.41	14	194	<2	21	0.46	<4	4	16	10	1.13	<0.01	11	0.62	507	<1	27	282	26	0.34	<5	<5	<10	53	1113	<2	21	<10	3	35
318251	1366370	<0.005	<1	1.68	13	199	<2	13	1.69	<4	12	43	19	2.72	<0.01	7	1.07	526	<1	33	490	8	0.12	<5	<5	<10	116	1907	<2	90	15	12	52

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, December 3, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 11/19/2012
 Date Completed: 11/30/2012
 Job #: 201244373
 Reference: TL 12 279
 Sample #: 165

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
318252	1366371	0.347	<1	0.11	18	181	<2	19	0.14	<4	9	19	24	0.99	<0.01	4	0.66	455	<1	35	329	55	0.57	<5	<5	<10	18	912	<2	17	<10	3	80
318253	1366372	0.056	<1	1.53	24	198	<2	21	0.33	<4	7	20	8	0.90	<0.01	7	0.49	303	<1	41	316	21	0.63	<5	<5	<10	42	976	<2	21	<10	3	33
318254	1366373	0.266	1	2.40	14	231	<2	11	0.59	<4	9	21	24	1.19	<0.01	9	0.88	617	<1	38	362	67	0.76	<5	<5	<10	54	1120	<2	24	<10	4	248
318255	1366374	0.224	1	3.57	19	201	<2	6	1.61	<4	6	18	26	1.57	0.03	12	1.61	1068	<1	26	345	90	0.70	<5	<5	<10	81	1194	<2	23	<10	5	368
318256	1366375	0.135	<1	2.17	10	146	<2	12	0.64	<4	3	16	6	1.12	<0.01	9	1.15	772	<1	25	308	18	0.43	<5	<5	<10	52	1103	<2	20	<10	4	46
318257	1366376	0.183	<1	2.52	10	157	<2	13	0.77	<4	3	14	6	1.16	<0.01	9	1.19	800	<1	27	310	19	0.47	<5	<5	<10	61	1122	<2	21	<10	4	46
318258	1366377	0.161	<1	2.36	11	215	<2	19	0.46	<4	5	21	8	0.96	<0.01	9	0.60	421	<1	29	347	16	0.50	<5	<5	<10	46	1203	<2	23	<10	4	35
318259	1366378	0.067	<1	1.99	10	216	<2	17	0.42	<4	3	14	6	0.56	<0.01	5	0.33	193	<1	25	273	12	0.30	<5	<5	<10	43	1022	<2	20	<10	3	19
318260	1366379	0.035	<1	1.39	12	149	<2	17	0.67	<4	5	13	9	0.75	<0.01	5	0.61	360	<1	17	219	6	0.23	<5	<5	<10	42	922	<2	23	<10	3	24
318261D	1366379	0.074	<1	1.95	10	192	<2	6	0.82	<4	6	18	11	0.94	<0.01	8	0.74	452	<1	21	271	14	0.30	<5	<5	<10	47	1164	<2	29	<10	3	29
318262	1366380	0.256	<1	<0.01	356	4976	<2	13	0.80	<4	5	17	25	2.44	<0.01	<1	0.04	<100	<1	19	<100	18	0.33	17	<5	<10	49	386	<2	13	39	5	17
318263	1366381	0.024	<1	0.98	13	178	<2	7	0.58	<4	3	9	4	0.63	<0.01	5	0.43	336	<1	16	218	8	0.29	<5	<5	<10	47	906	<2	17	<10	2	21
318264	1366382	0.022	<1	1.12	11	115	<2	19	0.50	<4	4	10	3	0.58	<0.01	6	0.65	413	<1	18	261	10	0.24	<5	<5	<10	29	860	<2	15	<10	3	21
318265	1366383	0.017	<1	1.47	7	150	<2	14	0.68	<4	5	10	8	0.81	0.04	5	0.88	582	<1	21	326	17	0.41	<5	<5	<10	32	904	<2	15	<10	3	32
318266	1366384	0.064	<1	2.00	26	182	<2	11	0.32	<4	5	11	6	0.85	<0.01	4	0.45	270	<1	23	263	37	0.83	<5	<5	<10	27	826	<2	14	<10	3	197
318267	1366385	1.491	4	1.20	71	127	<2	16	<0.01	11	5	13	30	1.88	<0.01	<1	0.14	<100	<1	25	199	367	2.27	7	<5	<10	17	631	<2	14	33	2	2963
318268	1366386	0.171	<1	1.78	33	166	<2	10	<0.01	<4	3	10	5	1.37	<0.01	2	0.15	<100	<1	20	252	37	1.61	<5	<5	<10	18	789	<2	15	<10	2	145
318269	1366387	0.181	1	1.87	23	135	<2	11	0.41	<4	4	13	3	0.95	<0.01	2	0.52	301	<1	19	284	22	0.90	<5	<5	<10	27	739	<2	13	<10	3	76
318270	1366388	0.043	<1	2.55	25	99	<2	8	1.43	<4	4	10	4	0.88	<0.01	6	0.90	588	<1	16	256	31	0.46	<5	<5	<10	63	843	<2	15	<10	3	47
318271	1366389	0.063	<1	1.94	17	93	<2	8	1.10	<4	4	19	5	0.84	<0.01	6	0.77	477	<1	25	265	18	0.41	<5	<5	<10	47	822	<2	14	<10	3	54

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, December 3, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 11/19/2012
 Date Completed: 11/30/2012
 Job #: 201244373
 Reference: TL 12 279
 Sample #: 165

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
318272D	1366389	0.095	<1	2.08	12	141	<2	13	1.06	<4	4	16	4	0.74	<0.01	7	0.63	424	<1	25	212	17	0.40	<5	<5	<10	54	835	<2	14	<10	3	50
318273	1366390	<0.005	<1	1.65	22	198	<2	10	1.73	<4	13	46	19	2.81	<0.01	8	1.11	544	<1	30	491	6	0.13	<5	<5	<10	113	1942	<2	94	16	13	48
318274	1366391	0.012	<1	2.03	14	168	<2	<1	0.96	<4	4	12	3	0.80	<0.01	9	0.68	407	<1	21	281	16	0.44	<5	<5	<10	52	988	<2	16	<10	3	68
318275	1366392	0.023	<1	1.59	22	141	<2	10	0.72	<4	4	10	6	0.67	<0.01	6	0.58	330	<1	21	244	33	0.39	<5	<5	<10	39	793	<2	14	<10	3	63
318276	1366393	0.006	<1	2.29	22	215	<2	13	1.15	<4	4	14	4	0.91	<0.01	6	0.63	412	<1	25	260	18	0.45	<5	<5	<10	61	985	<2	17	<10	3	37
318277	1366394	0.008	<1	2.38	24	201	<2	14	0.89	<4	4	12	5	1.04	<0.01	8	0.56	350	<1	27	290	18	0.57	<5	<5	<10	53	1050	<2	19	<10	3	69
318278	1366395	0.014	<1	1.52	29	170	<2	5	0.67	<4	4	13	8	1.29	<0.01	7	0.62	386	<1	30	308	19	0.75	<5	<5	<10	32	983	<2	16	<10	3	48
318279	1366396	0.016	<1	2.51	24	273	<2	15	0.88	<4	4	12	6	1.31	<0.01	10	0.59	397	<1	23	284	18	0.80	<5	<5	<10	57	1146	<2	20	<10	3	49
318280	1366397	0.011	1	2.03	15	231	<2	16	0.65	<4	5	15	10	1.01	<0.01	8	0.51	315	<1	28	311	18	0.47	<5	<5	<10	43	1034	<2	17	<10	4	50
318281	1366398	0.009	<1	2.63	8	300	<2	13	1.13	<4	5	15	9	1.25	<0.01	7	0.40	314	<1	27	317	9	0.46	<5	<5	<10	86	1208	<2	21	<10	3	123
318282	1366399	0.006	<1	5.21	13	350	<2	9	1.41	<4	4	12	8	1.08	<0.01	6	0.34	272	<1	18	308	14	0.37	<5	<5	<10	113	1290	<2	23	<10	5	120
318283R	1366399	0.010	<1	4.70	5	200	<2	10	0.69	<4	4	13	6	1.12	<0.01	3	0.35	284	<1	22	317	8	0.33	<5	<5	<10	47	1187	<2	21	<10	4	75
318284	1366400	1.895	<1	3.12	22	317	2	12	1.92	<4	14	46	28	3.11	<0.01	9	1.14	595	<1	34	514	8	0.12	<5	<5	<10	177	2032	<2	101	17	13	66
318285	1366401	0.011	<1	4.45	18	319	<2	11	1.33	<4	4	12	5	1.24	<0.01	9	0.52	321	<1	20	308	7	0.40	<5	<5	<10	109	1350	<2	24	<10	4	47
318286	1366402	0.005	<1	2.17	3	181	<2	10	1.06	<4	5	13	8	1.16	<0.01	8	0.61	311	<1	26	293	10	0.31	<5	<5	<10	61	1156	<2	21	<10	4	63
318287	1366403	0.035	<1	4.49	16	237	<2	9	1.93	<4	4	13	6	1.16	<0.01	11	1.04	529	<1	23	316	28	0.43	<5	<5	<10	93	1159	<2	20	<10	4	50
318288	1366404	0.026	<1	4.60	15	313	<2	12	1.78	<4	6	13	17	1.21	0.07	10	0.81	421	<1	22	403	55	0.65	<5	<5	<10	97	1274	<2	23	<10	5	126
318289	1366405	0.012	<1	2.01	29	250	<2	18	0.89	<4	7	12	13	1.06	0.12	5	0.43	251	<1	24	471	17	0.80	<5	<5	<10	53	1191	<2	24	<10	4	50
318290	1366406	0.017	<1	3.37	4	307	<2	14	0.91	<4	15	67	31	1.96	0.07	9	0.63	295	<1	51	539	16	0.79	<5	<5	<10	65	1705	<2	51	<10	10	70
318291	1366407	0.135	<1	4.84	27	380	2	20	2.08	<4	20	113	47	3.54	0.19	11	1.35	778	<1	73	456	26	1.56	<5	<5	<10	102	2165	<2	76	<10	14	90

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, December 3, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 11/19/2012
 Date Completed: 11/30/2012
 Job #: 201244373
 Reference: TL 12 279
 Sample #: 165

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
318292	1366408	0.347	2	3.77	48	485	2	17	1.04	5	7	32	120	2.41	0.14	9	0.67	453	<1	35	376	773	2.14	<5	<5	<10	61	1348	<2	32	20	6	1584
318293	1366409	0.028	<1	<0.01	10	19	<2	12	0.11	<4	<1	32	20	0.34	<0.01	<1	0.14	129	<1	41	<100	70	0.18	<5	<5	<10	10	162	<2	5	<10	2	112
318294D	1366409	0.020	<1	<0.01	13	23	<2	11	0.13	<4	1	34	21	0.35	<0.01	<1	0.14	133	<1	45	<100	72	0.17	<5	<5	<10	11	169	<2	5	<10	2	120
318295	1366410	<0.005	<1	2.87	14	270	<2	19	1.89	<4	13	44	19	2.75	<0.01	8	1.05	539	<1	31	490	7	0.12	<5	<5	<10	166	2019	<2	93	18	13	55
318296	1366411	0.149	<1	3.06	39	373	<2	17	1.20	<4	8	31	39	1.72	<0.01	7	0.88	708	<1	34	402	77	1.00	<5	<5	<10	51	1338	<2	29	<10	5	212
318297	1366412	0.640	<1	4.44	24	390	<2	20	1.12	<4	5	15	15	1.84	<0.01	11	0.85	699	<1	26	440	37	0.90	<5	5	<10	59	1498	<2	32	<10	5	138
318298	1366413	0.175	3	2.91	32	268	<2	16	1.44	<4	5	17	34	2.08	<0.01	8	0.92	700	<1	34	426	549	1.29	<5	<5	<10	57	1389	<2	30	<10	4	550
318299	1366414	0.195	<1	4.22	23	411	<2	6	1.22	5	4	18	45	1.25	0.17	15	1.11	498	<1	36	274	242	0.92	<5	<5	<10	45	1123	<2	26	17	4	1361
318300	1366415	2.397	4	2.98	33	323	<2	18	1.30	6	4	21	65	1.34	<0.01	9	1.13	497	<1	40	250	929	0.99	<5	<5	<10	56	921	<2	25	19	3	1520
318301	1366416	0.289	3	4.10	18	332	<2	19	1.41	6	4	19	35	1.30	0.08	11	1.06	465	<1	35	244	862	1.04	<5	<5	<10	61	943	<2	23	18	4	1371
318302	1366417	0.115	<1	4.30	20	348	<2	15	1.39	<4	5	21	9	1.12	<0.01	17	1.24	445	<1	39	281	60	0.66	<5	<5	<10	46	1120	<2	26	<10	4	88
318303	1366418	0.111	5	1.97	34	229	<2	14	0.49	<4	4	23	17	1.34	<0.01	6	0.47	177	<1	45	254	214	1.24	<5	<5	<10	20	762	<2	24	<10	3	456
318304	1366419	0.059	<1	3.68	21	276	2	23	0.64	<4	4	19	4	1.23	0.03	10	0.99	241	<1	38	300	56	0.89	<5	<5	<10	36	918	<2	26	<10	3	71
318305D	1366419	0.065	<1	3.35	31	265	2	9	0.63	<4	4	17	4	1.25	0.03	10	1.02	247	<1	32	310	56	0.92	<5	<5	<10	34	902	<2	24	<10	3	75
318306	1366420	4.894	64	3.40	27	414	<2	7	1.31	19	12	32	46	2.83	<0.01	8	0.70	454	<1	30	467	584	0.43	52	<5	216	185	1607	<2	81	54	12	1808
318307	1366421	0.265	3	3.77	64	220	2	18	0.33	6	11	67	94	2.37	<0.01	13	1.02	198	<1	63	381	386	2.03	<5	<5	<10	27	968	<2	55	21	5	1779
318308	1366422	0.143	<1	3.34	61	233	<2	17	0.42	<4	13	88	78	2.23	<0.01	9	0.77	211	<1	65	432	118	1.94	<5	<5	<10	33	866	<2	54	<10	6	243
318309	1366423	0.106	<1	3.55	42	213	<2	13	0.51	<4	17	118	36	3.33	0.08	21	1.94	458	<1	90	492	105	1.68	<5	<5	<10	37	1411	<2	79	<10	6	190
318310	1366424	0.089	1	3.79	15	217	2	20	0.42	<4	20	117	45	3.78	<0.01	26	2.10	524	<1	93	435	83	1.20	<5	<5	<10	30	1798	<2	96	<10	7	126
318311	1366425	0.684	4	3.67	53	240	2	9	0.65	6	15	112	43	3.27	0.12	13	0.95	309	<1	93	411	763	2.66	<5	<5	<10	36	1024	<2	71	22	8	1622

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, December 3, 2012

Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 11/19/2012
 Date Completed: 11/30/2012
 Job #: 201244373
 Reference: TL 12 279
 Sample #: 165

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
318312	1366426	1.398	7	3.67	38	334	2	19	0.59	5	13	96	52	2.71	0.08	15	1.24	345	<1	72	331	565	1.73	6	<5	<10	33	1205	<2	58	13	7	643
318313	1366427	0.212	4	2.59	22	263	<2	19	0.62	<4	13	84	66	2.46	0.17	13	1.43	336	<1	77	312	326	0.90	<5	<5	<10	30	1176	<2	56	<10	6	236
318314	1366428	14.459	46	2.94	51	266	<2	19	0.61	28	9	68	303	2.92	0.02	7	0.58	202	<1	71	290	4087	3.26	31	<5	<10	35	731	<2	54	107	5	12056
318315	1366429	0.050	<1	3.75	24	283	<2	22	1.23	<4	7	25	17	1.50	<0.01	9	1.30	363	<1	43	438	91	0.80	<5	<5	<10	46	1029	<2	36	<10	3	134
318316D	1366429	0.041	<1	4.22	33	298	<2	7	1.26	<4	6	34	17	1.52	<0.01	10	1.28	363	<1	58	448	86	0.76	<5	<5	<10	46	1066	<2	41	<10	4	133
318317	1366430	0.008	<1	1.93	17	226	<2	16	1.84	<4	13	47	20	2.90	<0.01	8	1.13	561	<1	30	499	7	0.11	<5	<5	<10	136	1996	<2	98	17	13	49
318318	1366431	0.093	<1	4.50	24	372	<2	14	0.22	<4	6	44	4	1.22	<0.01	5	0.34	<100	<1	65	457	74	0.97	<5	<5	<10	28	1101	<2	42	<10	4	62
318319	1366432	0.056	<1	3.79	56	311	<2	11	0.49	<4	5	25	50	1.27	<0.01	9	1.26	209	<1	40	338	68	0.82	<5	<5	<10	32	1003	<2	28	<10	3	356
318320	1366433	0.059	<1	4.64	36	366	<2	11	1.25	<4	5	28	18	1.34	<0.01	11	1.20	373	<1	49	304	38	0.96	<5	<5	<10	45	1078	<2	30	<10	4	128
318321	1366434	0.155	3	3.41	40	350	2	6	1.00	<4	4	21	13	1.23	<0.01	5	0.75	317	<1	36	323	176	0.97	<5	<5	<10	45	914	<2	23	<10	3	207
318322	1366435	0.031	<1	4.85	33	482	<2	13	0.57	<4	5	24	7	1.00	<0.01	5	0.44	145	<1	47	333	33	0.82	<5	<5	<10	37	1202	<2	31	<10	4	26
318323	1366436	0.091	<1	3.85	37	389	<2	18	0.44	<4	5	22	5	1.07	<0.01	4	0.39	124	<1	38	373	41	0.95	<5	<5	<10	29	1017	<2	27	<10	4	43
318324	1366437	0.512	2	4.32	57	320	<2	20	1.27	<4	7	40	18	1.52	0.05	7	0.81	332	<1	52	378	123	1.24	5	<5	<10	65	1031	<2	36	<10	5	57
318325	1366438	0.091	<1	3.71	62	383	2	19	1.14	<4	12	64	39	1.95	0.07	10	0.74	333	<1	70	475	98	1.62	5	<5	<10	40	1105	<2	53	<10	9	91
318326	1366439	0.364	11	4.20	57	685	2	15	1.02	<4	8	45	39	1.51	0.05	9	0.58	304	<1	60	397	58	1.19	5	<5	<10	46	1212	<2	45	<10	6	179
318327D	1366439	0.297	<1	3.98	59	675	<2	15	1.05	<4	9	47	41	1.56	<0.01	9	0.59	313	<1	66	417	61	1.23	<5	<5	<10	45	1210	<2	47	<10	6	179
318328	1366440	0.249	<1	<0.01	356	>5000	<2	17	0.80	<4	5	17	27	2.59	<0.01	<1	0.04	<100	<1	16	<100	15	0.35	17	<5	<10	62	505	<2	13	42	6	21
318329	1366441	1.494	7	3.89	49	429	<2	15	0.88	<4	6	45	69	1.34	0.15	7	0.56	337	<1	80	408	190	1.02	6	<5	<10	58	1158	<2	48	<10	5	372
318330	1366442	1.868	6	3.73	59	434	<2	19	1.16	<4	5	30	69	1.35	<0.01	9	0.74	453	<1	55	371	133	1.04	<5	<5	<10	65	1131	<2	38	<10	5	529
318331	1366443	0.394	2	2.94	42	332	<2	8	1.00	<4	5	35	18	1.18	<0.01	8	0.70	289	<1	57	320	121	0.81	<5	<5	<10	45	1023	<2	37	<10	5	148

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, December 3, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 11/19/2012
 Date Completed: 11/30/2012
 Job #: 201244373
 Reference: TL 12 279
 Sample #: 165

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
318332	1366444	0.676	5	5.02	25	336	<2	8	1.56	<4	11	57	63	2.25	<0.01	14	1.33	443	<1	60	426	177	0.89	<5	<5	<10	64	1645	<2	54	<10	8	197

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Friday, November 30, 2012

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 11/19/2012
 Date Completed: 11/30/2012
 Job #: 201244373
 Reference: TL 12 279
 Sample #: 165

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
318152	1366280	2120	0.062	2.120
318153	1366281	<5	<0.001	<0.005
318154	1366282	10	<0.001	0.010
318155	1366283	8	<0.001	0.008
318156	1366284	5	<0.001	0.005
318157	1366285	5	<0.001	0.005
318158	1366286	<5	<0.001	<0.005
318159	1366287	11	<0.001	0.011
318160	1366288	14	<0.001	0.014
318161	1366289	5	<0.001	0.005
318162 Dup	1366289	7	<0.001	0.007
318163	1366290	5	<0.001	0.005
318164	1366291	22	<0.001	0.022
318165	1366292	18	<0.001	0.018
318166	1366293	43	0.001	0.043
318167	1366294	13	<0.001	0.013
318168	1366295	16	<0.001	0.016
318169	1366296	17	<0.001	0.017
318170	1366297	15	<0.001	0.015
318171	1366298	23	<0.001	0.023
318172	1366299	34	<0.001	0.034
318173 Dup	1366299	32	<0.001	0.032
318174	1366300	5213	0.152	5.213
318175	1366301	57	0.002	0.057
318176	1366302	28	<0.001	0.028
318177	1366303	25	<0.001	0.025
318178	1366304	21	<0.001	0.021
318179	1366305	20	<0.001	0.020
318180	1366306	18	<0.001	0.018
318181	1366307	63	0.002	0.063

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Friday, November 30, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 11/19/2012
 Date Completed: 11/30/2012
 Job #: 201244373
 Reference: TL 12 279
 Sample #: 165

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
318182	1366308	17	<0.001	0.017
318183	1366309	21	<0.001	0.021
318184 Dup	1366309	13	<0.001	0.013
318185	1366310	<5	<0.001	<0.005
318186	1366311	13	<0.001	0.013
318187	1366312	16	<0.001	0.016
318188	1366313	17	<0.001	0.017
318189	1366314	46	0.001	0.046
318190	1366315	529	0.015	0.529
318191	1366316	725	0.021	0.725
318192	1366317	1133	0.033	1.133
318193	1366318	67	0.002	0.067
318194	1366319	43	0.001	0.043
318195 Dup	1366319	47	0.001	0.047
318196	1366320	257	0.007	0.257
318197	1366321	44	0.001	0.044
318198	1366322	269	0.008	0.269
318199	1366323	107	0.003	0.107
318200	1366324	26	<0.001	0.026
318201	1366325	<5	<0.001	<0.005
318202	1366326	<5	<0.001	<0.005
318203	1366327	7	<0.001	0.007
318204	1366328	105	0.003	0.105
318205	1366329	92	0.003	0.092
318206 Dup	1366329	93	0.003	0.093
318207	1366330	<5	<0.001	<0.005
318208	1366331	23	<0.001	0.023
318209	1366332	30	<0.001	0.030
318210	1366333	11	<0.001	0.011
318211	1366334	11	<0.001	0.011

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Friday, November 30, 2012

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 11/19/2012
 Date Completed: 11/30/2012
 Job #: 201244373
 Reference: TL 12 279
 Sample #: 165

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
318212	1366335	136	0.004	0.136
318213	1366336	82	0.002	0.082
318214	1366337	23	<0.001	0.023
318215	1366338	15	<0.001	0.015
318216	1366339	102	0.003	0.102
318217 Rep	1366339	86	0.003	0.086
318218	1366340	1769	0.052	1.769
318219	1366341	81	0.002	0.081
318220	1366342	53	0.002	0.053
318221	1366343	15	<0.001	0.015
318222	1366344	11	<0.001	0.011
318223	1366345	32	<0.001	0.032
318224	1366346	42	0.001	0.042
318225	1366347	38	0.001	0.038
318226	1366348	18	<0.001	0.018
318227	1366349	248	0.007	0.248
318228 Dup	1366349	206	0.006	0.206
318229	1366350	<5	<0.001	<0.005
318230	1366351	65	0.002	0.065
318231	1366352	628	0.018	0.628
318232	1366353	162	0.005	0.162
318233	1366354	187	0.005	0.187
318234	1366355	196	0.006	0.196
318235	1366356	169	0.005	0.169
318236	1366357	479	0.014	0.479
318237	1366358	265	0.008	0.265
318238	1366359	40	0.001	0.040
318239 Dup	1366359	36	0.001	0.036
318240	1366360	5226	0.152	5.226
318241	1366361	35	0.001	0.035

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Friday, November 30, 2012

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 11/19/2012
 Date Completed: 11/30/2012
 Job #: 201244373
 Reference: TL 12 279
 Sample #: 165

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
318242	1366362	22	<0.001	0.022
318243	1366363	13	<0.001	0.013
318244	1366364	1102	0.032	1.102
318245	1366365	1148	0.033	1.148
318246	1366366	450	0.013	0.450
318247	1366367	154	0.004	0.154
318248	1366368	45	0.001	0.045
318249	1366369	63	0.002	0.063
318250 Dup	1366369	51	0.001	0.051
318251	1366370	<5	<0.001	<0.005
318252	1366371	347	0.010	0.347
318253	1366372	56	0.002	0.056
318254	1366373	266	0.008	0.266
318255	1366374	224	0.007	0.224
318256	1366375	135	0.004	0.135
318257	1366376	183	0.005	0.183
318258	1366377	161	0.005	0.161
318259	1366378	67	0.002	0.067
318260	1366379	35	0.001	0.035
318261 Dup	1366379	74	0.002	0.074
318262	1366380	256	0.007	0.256
318263	1366381	24	<0.001	0.024
318264	1366382	22	<0.001	0.022
318265	1366383	17	<0.001	0.017
318266	1366384	64	0.002	0.064
318267	1366385	1491	0.043	1.491
318268	1366386	171	0.005	0.171
318269	1366387	181	0.005	0.181
318270	1366388	43	0.001	0.043
318271	1366389	63	0.002	0.063

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Friday, November 30, 2012

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 11/19/2012
 Date Completed: 11/30/2012
 Job #: 201244373
 Reference: TL 12 279
 Sample #: 165

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
318272 Dup	1366389	95	0.003	0.095
318273	1366390	<5	<0.001	<0.005
318274	1366391	12	<0.001	0.012
318275	1366392	23	<0.001	0.023
318276	1366393	6	<0.001	0.006
318277	1366394	8	<0.001	0.008
318278	1366395	14	<0.001	0.014
318279	1366396	16	<0.001	0.016
318280	1366397	11	<0.001	0.011
318281	1366398	9	<0.001	0.009
318282	1366399	6	<0.001	0.006
318283 Rep	1366399	10	<0.001	0.010
318284	1366400	1895	0.055	1.895
318285	1366401	11	<0.001	0.011
318286	1366402	5	<0.001	0.005
318287	1366403	35	0.001	0.035
318288	1366404	26	<0.001	0.026
318289	1366405	12	<0.001	0.012
318290	1366406	17	<0.001	0.017
318291	1366407	135	0.004	0.135
318292	1366408	347	0.010	0.347
318293	1366409	28	<0.001	0.028
318294 Dup	1366409	20	<0.001	0.020
318295	1366410	<5	<0.001	<0.005
318296	1366411	149	0.004	0.149
318297	1366412	640	0.019	0.640
318298	1366413	175	0.005	0.175
318299	1366414	195	0.006	0.195
318300	1366415	2397	0.070	2.397
318301	1366416	289	0.008	0.289

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Friday, November 30, 2012

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 11/19/2012
 Date Completed: 11/30/2012
 Job #: 201244373
 Reference: TL 12 279
 Sample #: 165

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
318302	1366417	115	0.003	0.115
318303	1366418	111	0.003	0.111
318304	1366419	59	0.002	0.059
318305 Dup	1366419	65	0.002	0.065
318306	1366420	4894	0.143	4.894
318307	1366421	265	0.008	0.265
318308	1366422	143	0.004	0.143
318309	1366423	106	0.003	0.106
318310	1366424	89	0.003	0.089
318311	1366425	684	0.020	0.684
318312	1366426	1398	0.041	1.398
318313	1366427	212	0.006	0.212
318314	1366428	14459	0.422	14.459
318315	1366429	50	0.001	0.050
318316 Dup	1366429	41	0.001	0.041
318317	1366430	8	<0.001	0.008
318318	1366431	93	0.003	0.093
318319	1366432	56	0.002	0.056
318320	1366433	59	0.002	0.059
318321	1366434	155	0.005	0.155
318322	1366435	31	<0.001	0.031
318323	1366436	91	0.003	0.091
318324	1366437	512	0.015	0.512
318325	1366438	91	0.003	0.091
318326	1366439	364	0.011	0.364
318327 Dup	1366439	297	0.009	0.297
318328	1366440	249	0.007	0.249
318329	1366441	1494	0.044	1.494
318330	1366442	1868	0.054	1.868
318331	1366443	394	0.012	0.394

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Friday, November 30, 2012


Preliminary Analysis

Treasury Metals Inc
Exchange Tower 130 King St Suite 3680
Toronto, On, CAN
M5X 1B1
Ph#: (416) 599-4133
Fax#: (416) 599-4959
Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 11/19/2012
Date Completed: 11/30/2012
Job #: 201244373
Reference: TL 12 279
Sample #: 165

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
318332	1366444	676	0.020	0.676

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


Certified By: Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, December 11, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 11/22/2012
 Date Completed: 12/05/2012
 Job #: 201244436
 Reference: TL 12-280
 Sample #: 101

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
322022	1366486	<0.005	<1	3.03	4	510	<2	18	1.43	<4	6	13	47	1.49	0.30	16	0.59	362	<1	68	400	31	0.23	<5	21	10	270	1639	<2	29	20	6	67
322023	1366487	<0.005	<1	3.07	6	362	<2	14	1.40	<4	6	14	35	1.39	0.25	17	0.55	316	<1	71	389	31	0.28	<5	22	<10	234	1565	<2	24	19	5	69
322024	1366488	<0.005	<1	3.25	5	368	<2	12	1.38	<4	5	14	11	1.38	0.30	18	0.58	332	<1	71	403	27	0.23	<5	22	<10	261	1593	<2	24	24	6	59
322025	1366489	<0.005	<1	2.56	4	301	<2	14	0.96	<4	5	15	8	1.27	0.34	13	0.53	265	<1	66	370	26	0.24	<5	13	<10	194	1475	<2	22	26	5	163
322026	1366490	<0.005	<1	2.93	4	254	<2	6	1.92	<4	13	48	24	3.07	0.31	11	1.27	591	<1	79	581	27	0.14	<5	14	10	156	2224	<2	98	38	14	52
322027	1366491	<0.005	<1	3.55	5	302	<2	20	1.26	<4	8	13	9	1.48	0.26	16	0.58	266	<1	68	404	30	0.32	<5	19	<10	283	1649	<2	25	22	5	64
322028	1366492	<0.005	<1	3.45	5	325	<2	4	1.33	<4	5	21	9	1.33	0.21	15	0.52	247	<1	86	422	25	0.18	<5	18	<10	336	1609	<2	23	20	5	32
322029	1366493	<0.005	<1	2.16	5	221	<2	10	1.02	<4	5	21	5	1.30	0.17	13	0.50	220	<1	92	392	24	0.16	<5	17	<10	269	1548	<2	22	19	5	24
322030	1366494	<0.005	<1	1.91	7	295	<2	14	1.10	<4	6	24	5	1.43	0.20	9	0.57	246	<1	91	473	27	0.23	<5	22	<10	307	1745	<2	26	22	5	58
322031	1366495	0.025	<1	4.27	16	368	<2	19	0.63	<4	5	21	13	1.26	0.24	12	0.60	345	<1	74	336	70	1.04	<5	16	<10	89	1156	<2	23	20	5	125
322032D	1366495	0.033	<1	5.90	18	460	<2	13	0.84	<4	7	26	16	1.49	0.28	17	0.72	414	<1	89	408	82	1.24	<5	25	<10	111	1415	<2	28	26	6	128
322033	1366496	0.043	<1	5.31	20	414	<2	4	0.76	<4	6	24	13	1.47	0.34	16	0.70	415	<1	83	395	77	1.22	<5	17	<10	97	1304	<2	26	26	6	115
322034	1366497	0.008	<1	3.30	11	290	<2	18	0.44	<4	4	17	9	0.49	0.23	4	0.20	<100	<1	59	252	42	0.48	<5	17	<10	78	1000	<2	23	20	4	24
322035	1366498	0.015	<1	3.24	14	241	<2	17	0.50	<4	5	10	10	0.35	0.38	6	0.20	<100	<1	52	250	40	0.37	<5	17	<10	82	1071	<2	22	20	4	46
322036	1366499	0.014	2	3.42	13	275	<2	17	0.70	<4	6	12	13	0.39	0.34	4	0.21	107	<1	66	348	47	0.40	<5	21	<10	99	1124	<2	24	21	5	70
322037	1366500	0.241	<1	0.43	349	>5000	<2	18	0.87	<4	4	17	31	2.60	0.29	3	0.16	<100	<1	66	<100	44	0.39	7	21	12	70	441	<2	13	61	6	21
322038	1366501	0.015	1	4.40	19	471	<2	14	0.68	<4	5	14	10	0.40	0.39	4	0.22	<100	<1	70	339	38	0.37	<5	21	<10	123	1203	<2	24	23	5	17
322039	1366502	0.019	2	3.35	9	321	<2	11	0.82	<4	5	13	15	0.29	0.40	5	0.20	<100	<1	68	263	34	0.30	<5	22	<10	106	959	<2	23	22	4	82
322040	1366503	0.016	<1	4.11	17	263	<2	13	1.44	<4	5	10	7	0.71	0.37	6	0.23	154	<1	57	305	37	0.69	<5	17	<10	137	1084	<2	24	20	5	55
322041	1366504	0.018	1	3.78	18	354	<2	11	1.14	<4	4	7	13	0.48	0.81	4	0.18	135	<1	60	330	42	0.44	<5	21	<10	147	1024	<2	25	20	4	38

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, December 11, 2012

Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 11/22/2012
 Date Completed: 12/05/2012
 Job #: 201244436
 Reference: TL 12-280
 Sample #: 101

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
322042	1366505	0.040	4	4.35	12	346	<2	11	0.88	<4	4	5	8	0.27	0.94	3	0.17	<100	<1	62	261	46	0.24	<5	20	<10	159	1174	<2	25	19	4	65
322043D	1366505	0.046	3	3.42	13	255	<2	19	0.62	<4	5	10	8	0.27	0.25	4	0.18	<100	<1	61	269	38	0.27	<5	22	<10	101	1069	<2	22	22	5	54
322044	1366506	0.043	4	4.51	14	383	<2	14	0.69	<4	6	14	6	0.32	0.31	6	0.22	104	<1	71	313	49	0.24	<5	23	<10	157	1260	<2	28	20	4	35
322045	1366507	0.036	3	3.64	9	316	<2	15	0.83	<4	4	25	7	0.36	0.32	6	0.23	142	<1	79	253	42	0.24	<5	27	<10	158	1021	<2	27	21	4	57
322046	1366508	0.013	<1	3.26	12	294	<2	16	1.57	<4	7	23	11	1.72	0.28	15	0.87	484	<1	86	463	45	0.78	<5	21	<10	144	1505	<2	35	21	6	72
322047	1366509	0.013	<1	3.89	12	323	<2	17	1.02	<4	2	17	10	0.86	0.31	12	0.87	459	<1	81	236	51	0.45	<5	21	<10	85	718	<2	18	25	4	52
322048	1366510	0.006	<1	3.16	6	268	<2	10	1.92	<4	13	46	23	2.93	0.35	11	1.23	572	<1	77	552	31	0.14	<5	19	<10	167	2150	<2	95	36	14	47
322049	1366511	0.021	<1	3.27	12	322	<2	13	0.76	<4	3	16	13	1.04	0.14	11	0.83	412	<1	69	231	49	0.55	<5	21	<10	67	709	<2	17	21	4	158
322050	1366512	0.028	<1	4.11	10	360	<2	5	0.53	<4	2	20	7	0.85	0.40	9	0.75	389	<1	79	246	37	0.42	<5	19	<10	59	634	<2	20	20	4	63
322051	1366513	0.092	<1	4.15	10	319	<2	23	0.97	<4	2	16	9	0.84	0.06	9	0.82	402	<1	71	213	42	0.42	<5	17	11	68	608	<2	16	22	3	59
322052	1366514	0.266	<1	3.87	19	356	<2	11	0.17	4	2	17	9	0.95	0.28	7	0.36	140	<1	63	193	54	0.97	<5	20	<10	42	637	<2	18	34	4	831
322053	1366515	0.196	<1	3.53	26	299	<2	5	0.25	<4	3	19	13	1.60	0.29	10	0.58	604	<1	80	222	64	1.42	<5	18	<10	51	508	<2	19	26	3	417
322054D	1366515	0.208	<1	3.10	26	260	<2	22	0.27	<4	3	16	13	1.55	0.60	9	0.56	552	<1	78	217	64	1.41	<5	20	<10	52	444	<2	16	26	3	400
322055	1366516	0.246	1	3.73	29	315	<2	9	0.22	5	3	24	15	1.85	0.25	11	0.57	700	<1	91	225	65	1.70	<5	19	<10	49	535	<2	22	32	4	696
322056	1366517	0.052	<1	3.11	21	281	<2	22	0.35	<4	2	18	6	0.90	0.32	11	0.77	791	<1	59	237	50	0.55	<5	22	<10	49	456	<2	14	21	3	79
322057	1366518	0.012	<1	3.90	8	252	<2	13	1.27	<4	3	18	7	0.96	0.31	14	1.21	916	<1	77	234	44	0.23	<5	17	<10	109	581	<2	16	24	3	57
322058	1366519	0.215	6	3.57	32	371	<2	24	1.38	6	4	19	137	1.96	0.39	11	0.99	707	<1	80	440	846	1.66	<5	18	<10	71	1016	<2	25	38	5	1269
322059	1366520	2.013	<1	3.40	5	301	<2	13	1.95	<4	14	50	46	3.31	0.25	13	1.33	638	<1	102	610	47	0.18	<5	19	<10	165	2169	<2	102	38	14	72
322060	1366521	0.112	1	3.33	19	254	<2	13	0.72	<4	8	27	70	2.11	0.03	15	1.01	837	<1	87	408	56	0.91	<5	13	<10	74	1458	<2	34	21	6	83
322061	1366522	4.226	<1	5.23	24	205	<2	9	1.84	<4	5	21	43	1.61	0.36	12	1.29	917	<1	84	359	128	1.16	<5	16	<10	130	1059	<2	29	26	5	360

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, December 11, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 11/22/2012
 Date Completed: 12/05/2012
 Job #: 201244436
 Reference: TL 12-280
 Sample #: 101

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
322062	1366523	3.857	4	3.56	40	227	<2	9	0.29	9	3	19	138	1.66	0.29	8	0.49	275	<1	78	301	850	1.82	<5	20	<10	48	1015	<2	24	61	4	2721
322063	1366524	0.423	3	3.17	23	267	<2	18	0.32	<4	5	21	33	0.99	0.08	9	0.63	429	<1	88	350	552	0.62	<5	26	<10	40	1179	<2	28	19	5	154
322064	1366525	0.397	<1	3.20	32	204	<2	11	0.76	<4	8	26	29	1.27	0.15	8	0.64	439	<1	88	396	84	0.87	<5	17	<10	58	1212	<2	29	21	5	130
322065D	1366525	0.341	<1	2.01	32	165	<2	14	0.61	<4	9	27	30	1.27	0.19	5	0.59	427	<1	91	375	81	0.87	<5	14	<10	44	1066	<2	28	22	5	164
322066	1366526	0.400	<1	5.72	29	269	<2	14	1.72	<4	5	22	26	1.58	0.19	12	1.00	710	<1	79	417	77	1.08	<5	20	<10	97	1384	<2	30	25	6	181
322067	1366527	0.144	<1	4.67	29	308	<2	15	1.21	<4	4	18	31	1.15	0.42	9	0.79	573	<1	56	332	87	0.64	<5	23	<10	82	1269	<2	26	29	4	97
322068	1366528	0.161	<1	4.25	26	232	<2	17	0.78	<4	4	20	21	1.23	0.40	5	0.63	411	<1	80	309	51	0.97	<5	17	<10	53	1112	<2	27	23	4	150
322069	1366529	0.195	<1	4.19	27	206	<2	9	0.85	<4	4	21	17	1.14	0.40	10	0.73	455	<1	84	341	69	0.96	<5	18	<10	50	1071	<2	26	22	4	133
322070	1366530	<0.005	<1	2.31	5	221	<2	7	1.83	<4	13	47	24	3.02	0.31	10	1.23	574	<1	79	597	28	0.15	<5	17	<10	135	2182	<2	98	38	13	48
322071	1366531	1.850	9	2.17	45	138	<2	18	<0.01	16	3	17	456	1.91	0.43	1	0.22	<100	<1	81	256	838	2.28	<5	26	<10	24	727	<2	20	71	4	3627
322072	1366532	0.075	<1	2.34	33	125	<2	21	0.81	<4	5	16	25	0.79	0.41	6	0.75	406	<1	74	371	108	0.58	<5	19	<10	37	826	<2	18	25	4	243
322073	1366533	0.314	2	3.53	37	178	<2	9	0.07	4	4	21	40	1.08	0.39	7	0.29	153	<1	76	204	276	1.20	<5	22	<10	32	940	<2	19	36	4	1033
322074	1366534	0.211	<1	3.60	32	181	<2	6	0.83	<4	3	14	15	0.99	0.35	9	0.61	356	<1	76	297	89	0.77	<5	20	<10	36	1029	<2	17	21	4	140
322075	1366535	0.075	<1	5.11	21	244	<2	22	1.27	<4	4	14	12	1.26	0.14	11	0.87	514	<1	76	348	62	0.99	<5	21	<10	71	1170	<2	19	26	5	72
322076D	1366535	0.056	<1	3.78	19	198	<2	20	1.14	<4	4	13	12	1.27	0.26	7	0.83	515	<1	80	335	65	1.00	<5	19	<10	59	1073	<2	17	21	4	74
322077	1366536	0.065	<1	5.11	19	236	<2	11	1.32	<4	4	19	14	1.25	0.27	11	0.91	547	<1	78	348	61	0.99	<5	21	<10	71	1156	<2	19	27	5	107
322078	1366537	0.087	2	4.85	26	379	<2	26	2.06	5	6	14	26	2.35	0.29	15	1.64	939	<1	76	489	544	1.43	<5	16	<10	91	1400	<2	26	38	5	1143
322079	1366538	0.044	<1	5.19	21	442	<2	18	1.48	<4	5	13	31	1.40	0.25	18	1.31	585	<1	70	338	73	0.79	<5	14	<10	90	1318	<2	20	24	5	147
322080	1366539	0.036	<1	4.65	9	326	<2	13	2.34	<4	4	13	6	0.91	0.36	18	0.81	335	<1	56	330	39	0.34	<5	20	<10	61	1339	<2	20	22	4	15
322081	1366540	5.284	66	1.09	31	256	<2	9	1.04	21	12	31	55	2.63	0.23	5	0.76	442	<1	71	494	628	0.42	20	14	221	106	1413	<2	71	81	11	1855

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, December 11, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 11/22/2012
 Date Completed: 12/05/2012
 Job #: 201244436
 Reference: TL 12-280
 Sample #: 101

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
322082	1366541	0.012	<1	4.70	9	391	<2	9	1.41	<4	3	11	9	1.02	0.13	17	0.90	324	<1	51	318	34	0.30	<5	22	<10	104	1378	<2	21	19	4	10
322083	1366542	0.012	<1	1.99	11	203	<2	18	1.59	<4	4	9	22	0.97	0.16	13	0.78	331	<1	48	291	34	0.35	<5	15	<10	42	1153	<2	17	19	3	5
322084	1366543	0.009	<1	4.20	10	372	<2	18	1.44	<4	4	10	10	1.13	0.01	16	1.12	409	<1	63	299	36	0.53	<5	22	<10	85	1206	<2	18	22	4	70
322085	1366544	0.465	5	4.00	52	199	<2	20	0.39	15	17	101	159	4.08	0.03	32	2.12	566	<1	118	419	1291	2.75	<5	19	<10	43	1140	<2	70	68	5	3548
322086	1366545	1.112	2	4.75	34	229	<2	7	0.26	<4	16	94	119	3.31	0.30	21	1.77	421	<1	112	410	364	1.88	<5	17	<10	41	1035	<2	63	27	7	216
322087R	1366545	1.136	4	4.37	34	227	<2	23	0.22	<4	16	102	122	3.36	0.21	20	1.75	421	<1	107	407	360	1.91	<5	14	<10	39	1016	<2	62	22	6	188
322088	1366546	8.705	7	4.64	76	208	<2	14	0.38	17	19	102	148	4.29	0.26	19	1.62	415	<1	135	379	862	3.32	<5	18	<10	48	1084	<2	68	70	6	3674
322089	1366547	0.147	9	4.21	44	200	<2	5	1.08	7	15	113	132	3.92	0.24	18	1.94	587	<1	130	758	1325	2.61	<5	16	<10	51	1243	<2	67	39	6	1257
322090	1366548	0.543	2	5.32	20	237	<2	8	0.99	<4	15	120	52	3.20	0.21	24	1.81	560	<1	113	514	162	1.26	<5	19	<10	58	1555	<2	63	24	9	237
322091	1366549	0.079	<1	4.26	29	201	<2	22	0.87	<4	15	110	30	3.11	0.17	25	1.98	466	<1	120	442	65	1.19	<5	21	<10	45	1298	<2	67	21	7	79
322092	1366550	<0.005	<1	3.50	8	270	<2	8	1.91	<4	13	51	24	3.00	0.09	12	1.30	565	<1	73	555	33	0.20	<5	16	<10	167	2070	<2	96	37	14	46
322093	1366551	0.199	1	4.82	30	207	<2	13	0.87	<4	17	113	35	3.53	0.17	23	1.95	543	<1	111	447	76	1.61	<5	13	<10	59	1376	<2	72	22	8	92
322094	1366552	1.862	8	4.65	60	217	<2	16	0.60	15	16	107	84	4.11	0.13	24	1.63	409	<1	124	413	254	3.07	<5	16	<10	47	1268	<2	68	62	7	3040
322095	1366553	0.099	1	4.01	25	231	<2	21	0.49	<4	14	112	40	3.01	0.54	34	2.16	465	<1	118	424	91	1.05	<5	18	<10	43	1504	<2	59	21	7	104
322096	1366554	0.274	2	3.88	39	233	<2	23	0.57	4	15	105	49	3.08	0.30	29	1.94	440	<1	115	403	163	1.43	<5	23	<10	44	1343	<2	58	22	6	274
322097	1366555	0.198	1	5.32	40	305	<2	5	1.10	<4	15	95	24	3.28	0.28	23	1.94	489	<1	129	429	115	1.74	<5	16	<10	66	1485	<2	66	19	7	161
322098D	1366555	0.153	1	6.04	43	332	<2	14	1.24	<4	16	106	27	3.62	0.21	27	2.14	543	<1	144	464	125	1.93	<5	17	<10	74	1603	<2	70	23	7	170
322099	1366556	0.282	2	5.91	44	326	<2	16	1.20	<4	16	94	24	3.43	0.36	26	2.05	516	<1	129	424	118	1.87	<5	15	<10	71	1559	<2	68	23	7	166
322100	1366557	0.371	1	6.11	31	268	2	7	1.29	4	6	33	47	2.04	0.20	27	1.86	319	<1	93	474	116	1.18	<5	17	<10	76	1028	<2	32	26	6	554
322101	1366558	0.175	1	4.83	24	298	<2	16	0.49	<4	16	111	24	3.22	0.31	25	1.90	387	<1	129	516	110	1.27	<5	15	<10	56	1570	<2	73	23	8	152

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By:  Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, December 11, 2012

Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 11/22/2012
 Date Completed: 12/05/2012
 Job #: 201244436
 Reference: TL 12-280
 Sample #: 101

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
322102	1366559	0.056	<1	4.76	16	341	<2	23	1.25	<4	15	103	34	3.22	0.16	21	1.94	467	<1	120	460	96	0.56	<5	17	<10	82	1809	<2	60	22	7	69
322103	1366560	0.252	<1	0.46	354	>5000	<2	26	0.86	<4	4	16	31	2.59	0.16	4	0.16	<100	<1	44	<100	38	0.43	7	18	<10	76	447	<2	12	57	7	17
322104	1366561	0.150	1	4.82	15	284	<2	13	0.81	<4	14	102	36	2.99	0.02	22	1.96	499	<1	136	485	79	0.80	<5	21	<10	63	1649	<2	59	23	8	116
322105	1366562	0.111	<1	4.82	44	279	<2	20	0.69	<4	7	41	11	1.42	0.13	10	0.71	200	<1	85	585	72	1.09	<5	20	<10	63	953	<2	27	22	6	42
322106	1366563	1.546	6	3.93	43	274	<2	13	0.69	7	5	30	32	1.64	0.20	11	0.68	235	<1	84	373	462	1.50	<5	20	<10	47	911	<2	20	48	5	1874
322107	1366564	0.453	3	5.10	10	260	<2	13	1.07	<4	16	115	88	2.97	0.20	18	1.43	528	<1	129	493	353	1.32	<5	20	<10	58	1656	<2	67	27	12	295
322108	1366565	0.877	7	4.76	18	220	<2	24	0.78	<4	15	96	108	3.16	0.22	18	1.46	525	<1	125	473	183	1.23	<5	18	<10	56	1672	<2	63	27	12	159
322109D	1366565	0.823	2	4.04	16	213	<2	17	0.74	<4	16	100	113	3.20	0.25	16	1.46	543	<1	135	478	198	1.21	<5	15	<10	49	1643	<2	62	26	11	176
322110	1366566	0.478	6	3.30	27	278	<2	10	1.02	5	16	90	70	3.16	0.25	13	1.22	564	<1	139	501	234	1.37	<5	21	<10	51	1662	<2	56	37	10	981
322111	1366567	2.748	40	3.01	61	1102	<2	7	0.12	4	3	21	67	0.76	0.12	5	0.24	<100	<1	75	347	676	0.73	17	20	11	36	1009	<2	21	44	4	1266
322112	1366568	0.542	3	2.87	35	602	<2	5	1.09	<4	5	24	17	1.23	0.17	7	0.66	422	<1	95	422	128	0.87	<5	18	<10	79	1047	<2	21	30	4	371
322113	1366569	0.318	<1	4.11	38	448	<2	15	1.46	<4	5	22	22	1.55	0.24	13	0.92	561	<1	84	405	78	1.20	<5	18	<10	94	1182	<2	23	25	5	79
322114	1366570	<0.005	<1	4.13	6	318	<2	18	2.14	<4	13	49	24	3.08	0.13	13	1.29	601	<1	83	575	30	0.17	<5	18	<10	199	2242	<2	101	38	15	48
322115	1366571	1.763	5	4.82	34	403	<2	12	1.31	7	5	22	49	1.44	0.05	15	0.83	544	<1	86	439	403	1.30	<5	17	10	93	1200	<2	23	50	6	1882
322116	1366572	0.619	<1	2.68	29	229	<2	21	1.29	<4	5	22	19	1.25	0.17	5	0.78	535	<1	92	429	103	0.93	<5	19	<10	72	940	<2	19	24	4	145
322117	1366573	0.366	2	3.85	35	252	<2	5	0.87	<4	6	23	25	1.31	0.21	10	0.66	271	<1	86	382	166	1.15	<5	21	<10	74	1047	<2	22	26	6	182
322118	1366574	0.186	1	9.71	64	518	2	15	4.24	<4	13	39	40	3.35	0.23	37	2.83	1276	<1	88	898	109	1.41	<5	14	<10	141	2778	<2	49	27	9	189
322119	1366575	0.270	<1	4.37	37	290	<2	19	1.71	<4	6	20	21	1.52	0.27	13	1.02	513	<1	88	467	100	0.99	<5	18	<10	74	1275	<2	24	29	6	370
322120D	1366575	0.299	<1	5.32	33	341	<2	19	1.79	<4	6	22	22	1.55	0.28	17	1.05	515	<1	86	485	99	1.03	<5	18	<10	81	1359	<2	26	28	6	382
322121	1366576	0.369	<1	3.57	32	233	<2	14	1.85	<4	7	17	23	1.54	0.15	11	0.99	518	<1	83	452	101	1.01	<5	18	<10	68	1144	<2	22	28	5	399

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, December 11, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 11/22/2012
 Date Completed: 12/05/2012
 Job #: 201244436
 Reference: TL 12-280
 Sample #: 101

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
322122	1366577	0.519	8	6.33	44	340	2	29	2.05	11	7	26	69	2.21	0.58	17	1.10	518	<1	101	573	868	1.87	<5	25	10	87	1338	<2	28	67	7	3307
322123	1366578	0.875	2	2.40	31	203	<2	18	1.07	4	5	15	29	1.45	0.17	9	0.71	345	<1	76	444	368	1.09	<5	18	<10	46	970	<2	18	28	4	584
322124	1366579	0.045	<1	5.85	22	394	<2	11	2.42	<4	6	18	8	1.62	0.08	16	1.43	651	<1	68	499	74	0.61	<5	19	<10	98	1507	<2	28	20	6	76
322125	1366580	2.140	<1	3.55	8	306	<2	11	1.93	<4	13	45	30	3.10	0.03	12	1.27	607	<1	76	562	32	0.17	<5	15	<10	164	2020	<2	97	36	14	51
322126	1366581	0.721	2	3.44	35	315	<2	9	0.83	<4	5	20	33	1.34	0.08	9	0.55	252	<1	84	424	513	1.09	<5	21	<10	65	1047	<2	24	30	6	381
322127	1366582	0.288	<1	3.82	25	370	<2	15	1.97	<4	4	15	22	1.56	0.26	10	1.15	651	<1	49	382	54	1.03	<5	24	11	80	1004	<2	20	28	5	291
322128	1366583	0.117	<1	4.12	21	339	<2	14	1.97	<4	5	15	11	1.41	0.11	13	1.11	588	<1	44	449	70	0.75	<5	19	<10	83	1179	<2	21	24	5	115
322129	1366584	0.341	<1	4.35	4	361	<2	15	1.98	<4	6	14	17	1.48	0.09	12	1.10	579	<1	53	459	76	0.63	<5	21	<10	80	1168	<2	22	23	5	105
322130	1366585	0.143	1	4.30	16	388	<2	11	1.83	<4	6	15	17	1.42	0.07	11	0.94	622	<1	59	451	441	0.77	<5	20	<10	81	1150	<2	20	28	5	294
322131D	1366585	0.181	1	3.72	18	363	<2	12	1.68	<4	6	16	16	1.35	0.10	10	0.88	597	<1	62	432	446	0.75	<5	17	<10	75	1116	<2	20	27	5	290
322132	1366586	0.402	1	7.90	35	588	2	28	2.89	<4	8	34	39	2.10	0.61	25	1.59	1160	<1	110	686	311	1.33	<5	25	<10	137	1705	<2	32	32	8	246

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Wednesday, December 5, 2012

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 11/22/2012
 Date Completed: 12/05/2012
 Job #: 201244436
 Reference: TL 12-280
 Sample #: 101

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
322022	1366486	<5	<0.001	<0.005
322023	1366487	<5	<0.001	<0.005
322024	1366488	<5	<0.001	<0.005
322025	1366489	<5	<0.001	<0.005
322026	1366490	<5	<0.001	<0.005
322027	1366491	<5	<0.001	<0.005
322028	1366492	<5	<0.001	<0.005
322029	1366493	<5	<0.001	<0.005
322030	1366494	<5	<0.001	<0.005
322031	1366495	25	<0.001	0.025
322032 Dup	1366495	33	<0.001	0.033
322033	1366496	43	0.001	0.043
322034	1366497	8	<0.001	0.008
322035	1366498	15	<0.001	0.015
322036	1366499	14	<0.001	0.014
322037	1366500	241	0.007	0.241
322038	1366501	15	<0.001	0.015
322039	1366502	19	<0.001	0.019
322040	1366503	16	<0.001	0.016
322041	1366504	18	<0.001	0.018
322042	1366505	40	0.001	0.040
322043 Dup	1366505	46	0.001	0.046
322044	1366506	43	0.001	0.043
322045	1366507	36	0.001	0.036
322046	1366508	13	<0.001	0.013
322047	1366509	13	<0.001	0.013
322048	1366510	6	<0.001	0.006
322049	1366511	21	<0.001	0.021
322050	1366512	28	<0.001	0.028
322051	1366513	92	0.003	0.092

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Wednesday, December 5, 2012

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 11/22/2012
 Date Completed: 12/05/2012
 Job #: 201244436
 Reference: TL 12-280
 Sample #: 101

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
322052	1366514	266	0.008	0.266
322053	1366515	196	0.006	0.196
322054 Dup	1366515	208	0.006	0.208
322055	1366516	246	0.007	0.246
322056	1366517	52	0.002	0.052
322057	1366518	12	<0.001	0.012
322058	1366519	215	0.006	0.215
322059	1366520	2013	0.059	2.013
322060	1366521	112	0.003	0.112
322061	1366522	4226	0.123	4.226
322062	1366523	3857	0.113	3.857
322063	1366524	423	0.012	0.423
322064	1366525	397	0.012	0.397
322065 Dup	1366525	341	0.010	0.341
322066	1366526	400	0.012	0.400
322067	1366527	144	0.004	0.144
322068	1366528	161	0.005	0.161
322069	1366529	195	0.006	0.195
322070	1366530	<5	<0.001	<0.005
322071	1366531	1850	0.054	1.850
322072	1366532	75	0.002	0.075
322073	1366533	314	0.009	0.314
322074	1366534	211	0.006	0.211
322075	1366535	75	0.002	0.075
322076 Dup	1366535	56	0.002	0.056
322077	1366536	65	0.002	0.065
322078	1366537	87	0.003	0.087
322079	1366538	44	0.001	0.044
322080	1366539	36	0.001	0.036
322081	1366540	5284	0.154	5.284

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Wednesday, December 5, 2012

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 11/22/2012
 Date Completed: 12/05/2012
 Job #: 201244436
 Reference: TL 12-280
 Sample #: 101

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
322082	1366541	12	<0.001	0.012
322083	1366542	12	<0.001	0.012
322084	1366543	9	<0.001	0.009
322085	1366544	465	0.014	0.465
322086	1366545	1112	0.032	1.112
322087 Rep	1366545	1136	0.033	1.136
322088	1366546	8705	0.254	8.705
322089	1366547	147	0.004	0.147
322090	1366548	543	0.016	0.543
322091	1366549	79	0.002	0.079
322092	1366550	<5	<0.001	<0.005
322093	1366551	199	0.006	0.199
322094	1366552	1862	0.054	1.862
322095	1366553	99	0.003	0.099
322096	1366554	274	0.008	0.274
322097	1366555	198	0.006	0.198
322098 Dup	1366555	153	0.004	0.153
322099	1366556	282	0.008	0.282
322100	1366557	371	0.011	0.371
322101	1366558	175	0.005	0.175
322102	1366559	56	0.002	0.056
322103	1366560	252	0.007	0.252
322104	1366561	150	0.004	0.150
322105	1366562	111	0.003	0.111
322106	1366563	1546	0.045	1.546
322107	1366564	453	0.013	0.453
322108	1366565	877	0.026	0.877
322109 Dup	1366565	823	0.024	0.823
322110	1366566	478	0.014	0.478
322111	1366567	2748	0.080	2.748

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Wednesday, December 5, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 11/22/2012
 Date Completed: 12/05/2012
 Job #: 201244436
 Reference: TL 12-280
 Sample #: 101

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
322112	1366568	542	0.016	0.542
322113	1366569	318	0.009	0.318
322114	1366570	<5	<0.001	<0.005
322115	1366571	1763	0.051	1.763
322116	1366572	619	0.018	0.619
322117	1366573	366	0.011	0.366
322118	1366574	186	0.005	0.186
322119	1366575	270	0.008	0.270
322120 Dup	1366575	299	0.009	0.299
322121	1366576	369	0.011	0.369
322122	1366577	519	0.015	0.519
322123	1366578	875	0.026	0.875
322124	1366579	45	0.001	0.045
322125	1366580	2140	0.062	2.140
322126	1366581	721	0.021	0.721
322127	1366582	288	0.008	0.288
322128	1366583	117	0.003	0.117
322129	1366584	341	0.010	0.341
322130	1366585	143	0.004	0.143
322131 Dup	1366585	181	0.005	0.181
322132	1366586	402	0.012	0.402

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, December 17, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/04/2012
 Date Completed: 12/13/2012
 Job #: 201244518
 Reference: TL 12 281
 Sample #: 102

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
328869	1366587	0.034	<1	1.88	9	247	<2	32	1.27	<4	3	22	26	0.99	<0.01	<1	0.57	588	<1	41	294	100	0.57	66	26	<10	82	814	<2	18	14	3	1005
328870	1366588	0.151	<1	4.34	20	373	<2	16	1.81	<4	6	33	59	1.47	<0.01	4	0.83	791	<1	58	431	86	0.92	99	20	<10	107	1192	<2	30	<10	5	217
328871	1366589	0.092	<1	6.16	26	405	<2	44	2.00	<4	6	40	35	1.56	0.02	13	0.92	785	<1	62	372	100	1.02	131	19	<10	109	1300	<2	28	<10	5	200
328872	1366590	0.009	<1	3.58	5	324	<2	41	2.12	<4	14	52	23	3.28	<0.01	9	1.26	646	<1	40	572	6	0.10	108	18	<10	177	2407	<2	110	18	14	53
328873	1366591	0.292	2	5.66	26	333	<2	22	1.77	14	5	34	237	1.70	<0.01	11	0.83	820	<1	64	319	1074	1.45	119	18	<10	102	1189	<2	23	59	4	4237
328874	1366592	0.058	<1	5.36	20	331	<2	40	1.37	<4	4	46	20	1.37	<0.01	9	0.78	688	<1	89	293	397	0.81	109	21	<10	77	1082	<2	20	15	4	760
328875	1366593	0.145	<1	4.21	14	243	<2	12	1.50	<4	5	24	12	1.29	<0.01	9	0.83	735	<1	46	288	110	0.83	90	20	<10	72	998	<2	18	<10	4	124
328876	1366594	0.279	2	4.80	24	345	<2	22	1.06	<4	4	38	93	1.43	<0.01	11	0.74	640	<1	69	296	614	1.01	99	24	<10	66	1093	<2	20	14	4	1050
328877	1366595	0.054	<1	3.87	9	278	<2	5	1.51	<4	3	28	26	1.12	<0.01	7	0.71	694	<1	52	247	151	0.62	97	23	<10	72	877	<2	16	<10	3	213
328878	1366596	0.034	<1	3.73	13	292	<2	62	1.41	<4	3	32	21	1.11	<0.01	6	0.70	657	<1	59	236	97	0.60	89	25	<10	72	844	<2	16	<10	3	222
328879D	1366596	0.028	<1	4.50	17	353	<2	24	1.71	<4	4	37	24	1.29	<0.01	7	0.81	750	<1	72	282	113	0.69	98	26	<10	88	926	<2	18	<10	3	254
328880	1366597	0.061	2	3.62	14	356	<2	36	0.60	<4	5	25	90	1.04	<0.01	4	0.31	240	<1	55	281	298	0.77	79	20	<10	69	955	<2	20	12	3	574
328881	1366598	0.012	<1	3.05	2	283	<2	38	0.74	<4	4	35	9	0.42	<0.01	3	0.23	192	<1	66	<100	20	0.14	74	24	<10	78	1107	<2	30	<10	3	26
328882	1366599	0.010	<1	3.70	6	305	<2	28	0.96	<4	7	41	21	0.43	0.05	5	0.20	274	<1	72	134	14	0.17	94	22	<10	91	1133	<2	33	<10	3	31
328883	1366600	5.066	68	3.11	30	407	<2	39	1.24	18	13	34	49	2.83	<0.01	6	0.73	477	<1	35	495	557	0.38	130	18	205	160	1646	<2	81	57	11	1746
328884	1366601	0.024	4	3.86	6	336	<2	17	0.75	<4	6	28	10	0.55	<0.01	5	0.23	167	<1	52	236	54	0.21	91	21	16	95	1367	<2	35	<10	4	179
328885	1366602	0.008	1	4.66	10	354	<2	32	0.85	<4	6	21	7	0.32	<0.01	4	0.13	114	<1	40	267	26	0.18	96	22	<10	107	1386	<2	30	<10	4	79
328886	1366603	0.042	7	3.95	14	331	<2	6	0.85	<4	6	26	32	0.43	<0.01	2	0.11	125	<1	47	270	47	0.27	93	22	<10	100	1385	<2	30	<10	4	166
328887	1366604	0.008	1	3.06	5	285	<2	22	0.75	<4	6	15	11	0.32	<0.01	2	0.10	106	<1	30	314	17	0.21	75	26	<10	87	1206	<2	27	<10	3	59
328888	1366605	0.008	<1	3.26	10	323	<2	20	0.78	<4	6	44	12	0.50	<0.01	3	0.11	113	<1	89	313	6	0.20	78	24	<10	94	1199	<2	30	<10	4	40

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, December 17, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/04/2012
 Date Completed: 12/13/2012
 Job #: 201244518
 Reference: TL 12 281
 Sample #: 102

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
328889	1366606	0.010	<1	2.04	6	243	<2	42	0.64	<4	5	25	7	0.43	<0.01	<1	0.14	141	<1	52	195	17	0.22	59	25	<10	76	993	<2	21	<10	3	60
328890D	1366606	0.006	<1	2.27	7	254	<2	30	0.66	<4	4	19	5	0.36	<0.01	<1	0.12	119	<1	39	182	9	0.20	62	21	<10	92	960	<2	20	<10	3	42
328891	1366607	0.006	<1	2.48	3	313	<2	12	0.63	<4	6	21	7	0.64	<0.01	1	0.24	167	<1	45	307	13	0.32	75	23	<10	122	1054	<2	22	<10	3	31
328892	1366608	0.073	<1	2.98	7	355	<2	27	1.79	<4	6	25	11	1.49	<0.01	8	0.51	487	<1	53	390	22	0.51	81	17	<10	181	1473	<2	28	<10	5	48
328893	1366609	0.011	<1	1.63	7	298	<2	30	0.98	<4	7	31	9	1.77	<0.01	8	0.60	472	<1	57	450	25	0.60	68	15	<10	109	1650	<2	31	<10	6	66
328894	1366610	<0.005	<1	2.37	<2	264	<2	12	1.89	<4	15	50	22	3.18	<0.01	7	1.22	615	<1	40	558	1	0.09	92	23	<10	139	2240	<2	105	15	13	52
328895	1366611	0.013	<1	2.64	2	447	<2	15	1.40	<4	7	41	11	1.68	<0.01	10	0.66	454	<1	73	449	22	0.41	78	21	<10	168	1616	<2	32	<10	6	54
328896	1366612	0.017	<1	3.32	4	477	<2	10	1.28	<4	8	33	22	1.82	<0.01	15	0.76	471	<1	61	471	21	0.36	93	16	<10	150	1757	<2	33	<10	5	253
328897	1366613	1.969	7	3.40	31	492	<2	29	0.30	<4	7	28	256	1.55	<0.01	5	0.32	221	<1	49	366	918	1.31	83	23	<10	36	1307	<2	24	17	4	1259
328898	1366614	0.180	1	2.05	23	327	<2	38	<0.01	12	3	35	15	1.27	0.02	<1	0.23	239	<1	73	185	53	1.20	55	20	<10	21	533	<2	12	45	2	3276
328899	1366615	0.058	<1	4.12	19	342	<2	27	1.30	<4	6	24	7	1.20	<0.01	7	0.87	598	<1	47	502	37	0.56	89	19	<10	57	1280	<2	22	<10	4	116
328900	1366616	0.051	<1	4.89	19	417	<2	39	1.54	<4	6	38	7	1.34	0.02	9	0.94	674	<1	75	585	39	0.55	113	25	<10	64	1528	<2	25	<10	5	69
328901D	1366616	0.047	<1	3.85	14	396	<2	51	1.32	<4	5	31	6	1.17	<0.01	6	0.83	583	<1	63	500	39	0.48	92	19	<10	61	1222	<2	22	<10	4	60
328902	1366617	2.430	4	2.89	29	346	<2	49	0.71	9	4	27	158	1.82	<0.01	2	0.58	435	<1	60	450	330	1.58	101	18	<10	45	1062	<2	19	37	4	2570
328903	1366618	0.092	<1	3.37	20	336	<2	41	0.96	<4	5	47	37	1.35	<0.01	5	0.71	702	<1	75	520	66	0.71	85	23	<10	61	1204	<2	21	<10	5	281
328904	1366619	0.697	2	3.99	13	298	<2	11	0.93	<4	8	41	31	1.53	0.07	9	1.08	1043	<1	84	546	211	0.58	104	22	<10	68	1399	<2	26	18	5	963
328905	1366620	0.251	4	3.84	41	354	<2	23	0.56	5	11	40	42	2.15	0.27	9	0.57	487	<1	87	386	697	1.80	97	22	<10	59	1234	<2	27	33	4	2230
328906	1366621	0.286	5	4.48	49	613	<2	20	0.66	6	13	47	47	2.46	0.50	11	0.64	552	<1	99	435	777	1.99	115	27	<10	66	1449	<2	30	40	4	2471
328907	1366622	1.345	3	3.68	17	354	<2	34	0.71	<4	8	43	253	1.18	0.09	10	0.83	756	<1	89	408	537	0.56	96	23	<10	68	1301	<2	26	17	4	669
328908	1366623	0.186	<1	3.50	21	401	<2	58	0.37	<4	10	41	33	1.09	<0.01	9	0.58	494	<1	78	424	134	0.56	88	25	<10	72	1376	<2	29	<10	4	92

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, December 17, 2012

Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 12/04/2012
 Date Completed: 12/13/2012
 Job #: 201244518
 Reference: TL 12 281
 Sample #: 102

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
328909	1366624	0.180	<1	3.91	22	436	<2	50	0.38	<4	12	41	35	2.24	<0.01	12	0.88	690	<1	75	491	31	1.34	94	24	<10	81	1513	<2	33	<10	5	90
328910	1366625	0.998	<1	3.24	12	409	<2	27	0.23	<4	7	38	38	1.49	<0.01	8	0.58	602	<1	57	458	15	0.79	79	24	<10	62	1233	<2	30	<10	4	63
328911	1366626	0.601	<1	2.95	22	331	<2	36	0.20	<4	9	38	34	2.01	<0.01	7	0.62	712	<1	72	426	20	1.13	80	18	<10	48	1334	<2	30	<10	5	62
328912D	1366626	0.596	<1	2.64	22	268	<2	18	0.20	<4	7	28	26	1.56	<0.01	4	0.46	534	<1	54	325	14	0.88	64	20	<10	53	1003	<2	24	<10	4	49
328913	1366627	0.028	<1	1.66	18	386	<2	27	0.36	<4	4	21	8	0.99	<0.01	5	0.59	435	<1	39	363	23	0.38	49	16	<10	37	893	<2	19	<10	3	54
328914	1366628	0.016	<1	2.66	12	198	<2	53	0.28	<4	7	30	4	0.94	<0.01	7	0.54	360	<1	64	359	23	0.54	65	18	<10	29	1260	<2	23	<10	3	80
328915	1366629	0.101	<1	3.03	21	228	<2	31	0.40	<4	10	42	32	1.18	<0.01	10	0.66	461	<1	73	483	66	0.61	77	21	<10	40	1447	<2	31	<10	5	136
328916	1366630	<0.005	<1	2.32	5	247	<2	59	1.74	<4	15	49	24	3.04	<0.01	7	1.18	598	<1	43	565	10	0.12	87	15	<10	126	2170	<2	100	13	12	59
328917	1366631	0.101	<1	3.38	31	259	<2	44	0.64	<4	11	53	13	1.61	<0.01	9	0.72	523	<1	74	412	13	1.00	81	25	<10	48	1490	<2	37	<10	5	103
328918	1366632	0.041	<1	4.21	10	281	<2	21	0.67	<4	6	30	4	1.09	<0.01	9	0.87	577	<1	49	354	20	0.70	97	24	<10	48	1327	<2	24	<10	4	44
328919	1366633	0.328	2	4.37	67	277	<2	31	0.20	<4	11	70	22	2.49	<0.01	5	0.44	231	<1	90	402	57	2.44	98	27	<10	32	1338	<2	42	<10	6	83
328920	1366634	0.877	5	3.10	49	199	<2	28	<0.01	7	5	42	26	1.64	<0.01	1	0.26	103	<1	76	272	492	1.62	84	20	<10	19	897	<2	20	31	3	2278
328921	1366635	0.204	1	4.68	29	241	<2	24	0.23	<4	7	34	15	1.31	<0.01	6	0.47	223	<1	67	329	62	1.15	98	28	<10	31	1137	<2	22	<10	3	467
328922	1366636	0.162	1	4.35	18	240	<2	33	0.21	<4	6	31	11	1.04	<0.01	7	0.51	239	<1	64	349	37	0.85	98	23	<10	29	1163	<2	22	10	3	297
328923D	1366636	0.134	1	3.45	21	207	<2	25	0.16	12	5	25	25	0.94	<0.01	4	0.45	215	<1	53	303	39	0.87	85	22	<10	27	1013	<2	19	36	3	2501
328924	1366637	0.222	2	4.57	25	247	<2	32	0.12	<4	5	27	13	0.92	<0.01	5	0.40	179	<1	50	302	39	0.77	96	27	<10	28	1176	<2	22	10	3	477
328925	1366638	2.182	43	5.30	35	220	<2	22	1.76	<4	5	43	12	1.15	<0.01	9	1.25	882	<1	68	352	90	0.42	119	26	<10	69	1173	<2	23	10	4	704
328926	1366639	0.058	<1	3.90	14	178	<2	21	1.09	<4	5	31	7	0.92	<0.01	5	0.74	508	<1	56	273	23	0.32	86	21	<10	50	988	<2	19	<10	3	57
328927	1366640	2.030	6	4.68	2243	494	2	42	6.04	8	108	271	3673	5.92	<0.01	13	1.48	689	14	1880	749	318	1.86	245	23	12	168	1112	<2	142	32	18	1084
328928	1366641	0.064	<1	3.10	34	207	3	50	2.78	5	23	62	173	4.26	<0.01	8	1.32	650	2361	60	471	31	0.33	121	25	<10	103	4672	<2	131	19	23	866

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, December 17, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/04/2012
 Date Completed: 12/13/2012
 Job #: 201244518
 Reference: TL 12 281
 Sample #: 102

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
328929	1366642	0.070	4	4.99	8	271	<2	22	2.18	<4	4	38	15	1.47	<0.01	6	1.06	700	<1	70	280	52	0.40	111	21	<10	77	1134	<2	20	<10	4	133
328930	1366643	0.018	<1	5.41	3	306	<2	36	1.95	<4	5	38	7	1.49	<0.01	8	1.13	671	<1	65	341	18	0.35	121	22	<10	81	1133	<2	22	<10	4	37
328931	1366644	1.783	1	5.88	18	459	<2	33	2.55	<4	18	107	88	3.16	<0.01	10	1.33	771	<1	94	486	36	1.47	144	26	<10	115	1874	<2	60	<10	10	90
328932	1366645	3.301	9	5.18	61	690	<2	30	1.68	11	13	95	415	3.35	<0.01	9	0.92	666	24	99	472	3160	2.85	134	19	<10	81	1866	<2	55	53	9	3564
328933	1366646	0.251	<1	4.23	42	424	<2	46	1.52	<4	8	62	65	1.97	<0.01	7	0.96	743	<1	74	452	188	1.34	107	18	<10	65	1340	<2	34	<10	6	330
328934R	1366646	0.246	<1	5.65	43	561	<2	27	1.69	<4	9	64	72	2.12	<0.01	9	1.04	815	<1	93	472	210	1.45	122	26	<10	71	1552	<2	39	10	7	336
328935	1366647	0.064	<1	4.83	26	363	<2	22	1.48	<4	4	31	9	1.77	<0.01	6	0.85	672	<1	58	501	20	0.94	107	22	<10	73	1443	<2	27	<10	5	208
328936	1366648	0.089	<1	1.37	4	261	<2	40	0.39	<4	3	24	16	0.80	<0.01	<1	0.59	300	<1	42	180	45	0.31	58	18	<10	37	751	<2	13	<10	2	74
328937	1366649	0.041	2	3.50	8	401	<2	30	1.93	<4	4	36	37	1.42	<0.01	10	1.54	945	3	63	255	678	0.55	92	21	<10	69	1199	<2	23	18	5	932
328938	1366650	<0.005	<1	3.69	4	340	<2	16	2.12	<4	14	51	25	3.17	0.01	9	1.28	672	<1	40	544	47	0.13	102	21	<10	179	2336	<2	105	17	13	130
328939	1366651	0.029	<1	4.03	2	573	<2	52	0.92	<4	6	39	21	1.56	<0.01	12	0.93	482	<1	66	322	19	0.36	88	18	<10	62	1493	<2	30	<10	4	57
328940	1366652	0.052	<1	4.47	30	620	<2	32	1.46	<4	5	27	22	1.30	<0.01	12	1.40	627	<1	50	236	109	0.46	102	24	<10	80	1081	<2	20	<10	4	228
328941	1366653	0.013	2	4.57	4	480	<2	50	1.82	<4	5	29	29	1.37	<0.01	13	1.84	724	2	47	299	541	0.44	111	22	<10	87	1086	<2	19	16	4	876
328942	1366654	3.509	9	4.70	6	428	<2	31	2.02	10	4	34	442	2.38	<0.01	13	1.65	884	6	62	280	1087	1.55	129	25	<10	77	1057	<2	22	42	7	2862
328943	1366655	0.384	2	5.23	18	466	<2	31	1.30	7	5	27	110	1.58	0.04	17	1.40	576	<1	42	326	292	1.13	121	23	<10	58	1212	<2	21	26	4	1646
328944	1366656	0.671	<1	3.44	9	294	<2	6	0.89	<4	4	21	52	1.03	0.09	12	0.97	394	4	35	202	130	0.65	81	13	<10	37	777	<2	14	<10	2	530
328945D	1366656	0.603	2	3.35	15	345	<2	48	1.02	<4	4	24	71	1.31	<0.01	11	1.22	495	<1	47	253	190	0.83	79	17	<10	44	953	<2	17	13	3	711
328946	1366657	0.885	4	0.03	20	103	<2	64	0.61	5	4	18	168	1.36	<0.01	<1	0.92	379	<1	37	275	768	1.16	46	17	<10	30	403	<2	8	23	2	1582
328947	1366658	0.751	3	4.72	23	354	<2	29	1.07	<4	5	33	37	1.68	<0.01	12	1.06	420	<1	55	333	340	1.41	103	22	<10	44	1004	<2	20	10	4	660
328948	1366659	0.291	1	4.59	24	405	<2	15	0.36	<4	5	39	16	1.61	0.06	9	0.56	185	<1	65	361	81	1.36	93	24	<10	28	1122	<2	22	<10	4	255

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, December 17, 2012

Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 12/04/2012
 Date Completed: 12/13/2012
 Job #: 201244518
 Reference: TL 12 281
 Sample #: 102

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
328949	1366660	5.145	67	2.84	33	399	<2	31	1.18	19	13	34	50	2.90	<0.01	6	0.75	472	<1	33	501	571	0.45	122	18	207	150	1606	<2	80	53	11	1798
328950	1366661	0.079	3	5.23	18	386	<2	14	1.22	<4	6	32	13	1.49	<0.01	12	1.07	419	<1	53	344	77	0.86	108	29	14	46	1141	<2	25	<10	4	158
328951	1366662	0.084	<1	4.86	20	376	<2	36	0.48	<4	6	49	7	1.46	0.01	7	0.71	195	<1	79	518	39	0.95	96	24	<10	30	1057	<2	24	<10	4	48
328952	1366663	0.491	<1	3.81	61	252	<2	29	0.36	<4	14	106	48	2.94	<0.01	14	1.68	398	5	99	504	161	1.71	95	15	<10	30	902	<2	55	<10	7	434
328953	1366664	2.520	13	2.43	80	213	<2	52	<0.01	28	10	87	318	3.99	<0.01	3	0.48	159	<1	101	326	1387	4.18	90	15	<10	24	677	<2	38	122	6	491
328954	1366665	0.105	1	4.54	36	241	2	18	0.61	<4	17	148	54	3.40	0.04	20	1.88	508	11	116	489	122	1.73	107	26	<10	48	1366	<2	67	<10	7	452
328955	1366666	0.082	<1	3.26	25	200	<2	20	0.54	<4	17	114	36	3.25	<0.01	16	1.76	461	4	93	431	82	1.45	85	25	<10	41	1339	<2	59	<10	7	121
328956D	1366666	0.088	<1	4.04	22	227	2	41	0.66	<4	18	128	41	3.64	0.05	20	2.00	522	11	106	481	91	1.61	100	13	<10	44	1524	<2	66	<10	8	138
328957	1366667	0.156	2	3.90	42	249	<2	31	0.73	<4	14	88	33	3.05	0.10	11	1.24	411	<1	99	499	189	2.01	100	18	<10	40	1161	<2	51	<10	7	353
328958	1366668	1.134	3	2.85	34	200	<2	19	0.38	<4	15	84	28	3.04	0.15	8	1.17	352	<1	99	449	140	1.60	82	18	<10	26	1116	<2	48	<10	5	353
328959	1366669	0.373	3	3.74	62	262	2	30	0.67	<4	19	130	63	3.50	0.02	12	1.43	467	2	118	499	159	1.96	102	16	<10	38	1263	<2	68	<10	7	165
328960	1366670	<0.005	<1	3.12	2	314	<2	6	1.99	<4	15	57	32	3.36	<0.01	8	1.29	637	<1	44	577	13	0.19	96	18	<10	165	2286	<2	108	19	13	63
328961	1366671	0.409	2	4.00	51	277	<2	28	0.62	<4	19	121	79	3.63	<0.01	15	1.47	494	<1	96	500	91	2.07	101	18	<10	41	1353	<2	69	16	9	903
328962	1366672	4.781	7	3.85	46	296	<2	41	0.79	41	8	38	110	2.67	<0.01	9	1.14	361	<1	56	417	177	2.58	108	21	<10	37	1005	<2	31	140	4	13852
328963	1366673	0.111	<1	4.26	17	357	<2	21	0.57	<4	7	41	18	1.37	<0.01	4	0.89	233	<1	70	561	66	0.68	94	14	<10	32	1061	<2	28	<10	4	268
328964	1366674	0.042	<1	4.93	21	351	<2	19	1.22	<4	7	42	21	1.59	0.02	5	1.08	368	<1	65	516	78	0.83	106	24	<10	51	1121	<2	29	<10	5	94
328965	1366675	0.242	2	3.53	32	343	<2	47	0.19	<4	7	49	52	1.38	0.07	2	0.44	132	<1	82	489	186	0.95	86	20	<10	25	1048	<2	27	<10	4	339
328966	1366676	0.373	4	4.22	39	382	<2	42	0.16	<4	8	37	72	1.54	0.11	3	0.43	128	<1	65	479	168	1.20	92	21	<10	27	1185	<2	29	16	5	432
328967D	1366676	0.365	3	3.67	39	358	<2	31	0.15	<4	8	36	76	1.62	0.13	2	0.44	131	<1	65	493	162	1.26	87	18	<10	26	1117	<2	27	10	4	454
328968	1366677	1.012	7	1.93	48	325	<2	29	<0.01	<4	6	28	29	1.10	<0.01	<1	0.23	<100	<1	46	283	349	1.00	56	14	<10	13	806	<2	18	11	3	751

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, December 17, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/04/2012
 Date Completed: 12/13/2012
 Job #: 201244518
 Reference: TL 12 281
 Sample #: 102

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
328969	1366678	0.198	<1	2.87	31	316	<2	15	0.65	<4	6	25	21	1.29	0.07	2	0.65	285	<1	47	470	57	0.92	72	26	<10	34	1017	<2	22	<10	4	102
328970	1366679	0.539	3	2.56	39	332	<2	25	0.97	<4	6	38	18	1.46	0.22	1	0.76	366	<1	63	396	115	1.08	77	22	<10	40	831	<2	18	18	4	701
328971	1366680	0.229	<1	<0.01	396	>5000	<2	36	0.78	<4	5	19	35	2.88	<0.01	<1	0.08	<100	<1	24	<100	25	0.34	65	24	<10	57	355	<2	14	40	5	48
328972	1366681	0.200	2	3.21	44	575	<2	57	0.55	<4	4	37	15	1.13	<0.01	6	0.52	192	<1	55	303	115	0.78	79	27	<10	45	841	<2	17	<10	4	53
328973	1366682	0.328	2	2.96	88	337	<2	16	<0.01	<4	12	87	34	2.05	<0.01	2	0.24	<100	<1	84	402	112	1.91	69	18	<10	22	1069	<2	43	<10	6	161
328974	1366683	0.104	2	3.48	48	458	<2	48	0.97	<4	9	55	49	1.84	<0.01	7	0.75	416	<1	62	409	137	1.19	80	20	<10	42	1202	<2	36	<10	6	222
328975	1366684	0.347	<1	3.59	38	415	<2	37	1.37	<4	7	35	25	1.56	<0.01	8	0.86	595	<1	46	440	50	0.84	89	18	<10	54	1303	<2	26	<10	4	71
328976	1366685	0.372	<1	3.99	33	403	<2	20	1.28	<4	7	36	39	1.66	<0.01	8	0.85	510	<1	54	443	96	1.09	89	18	<10	65	1392	<2	31	<10	5	277
328977	1366686	0.464	2	3.48	27	253	<2	20	1.24	<4	4	34	42	1.12	0.30	9	0.73	487	3	46	359	60	0.67	89	17	<10	44	890	<2	21	12	3	287
328978D	1366686	0.503	2	2.99	30	307	<2	31	1.42	<4	6	38	57	1.30	<0.01	7	0.93	618	<1	57	406	67	0.78	81	23	<10	50	1161	<2	24	<10	4	353
328979	1366687	0.495	2	2.28	40	238	<2	21	1.29	<4	6	33	51	1.64	0.04	3	0.88	419	<1	49	414	297	1.17	72	20	<10	50	979	<2	23	<10	4	293
328980	1366688	0.065	<1	4.66	21	330	2	41	2.10	<4	7	36	15	1.58	0.04	12	1.25	532	<1	56	485	70	0.72	103	20	<10	76	1339	<2	28	<10	5	95

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, December 13, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/04/2012
 Date Completed: 12/13/2012
 Job #: 201244518
 Reference: TL 12 281
 Sample #: 102

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
328869	1366587	34	<0.001	0.034
328870	1366588	151	0.004	0.151
328871	1366589	92	0.003	0.092
328872	1366590	9	<0.001	0.009
328873	1366591	292	0.009	0.292
328874	1366592	58	0.002	0.058
328875	1366593	145	0.004	0.145
328876	1366594	279	0.008	0.279
328877	1366595	54	0.002	0.054
328878	1366596	34	<0.001	0.034
328879 Dup	1366596	28	<0.001	0.028
328880	1366597	61	0.002	0.061
328881	1366598	12	<0.001	0.012
328882	1366599	10	<0.001	0.010
328883	1366600	5066	0.148	5.066
328884	1366601	24	<0.001	0.024
328885	1366602	8	<0.001	0.008
328886	1366603	42	0.001	0.042
328887	1366604	8	<0.001	0.008
328888	1366605	8	<0.001	0.008
328889	1366606	10	<0.001	0.010
328890 Dup	1366606	6	<0.001	0.006
328891	1366607	6	<0.001	0.006
328892	1366608	73	0.002	0.073
328893	1366609	11	<0.001	0.011
328894	1366610	<5	<0.001	<0.005
328895	1366611	13	<0.001	0.013
328896	1366612	17	<0.001	0.017
328897	1366613	1969	0.057	1.969
328898	1366614	180	0.005	0.180

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, December 13, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/04/2012
 Date Completed: 12/13/2012
 Job #: 201244518
 Reference: TL 12 281
 Sample #: 102

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
328899	1366615	58	0.002	0.058
328900	1366616	51	0.001	0.051
328901 Dup	1366616	47	0.001	0.047
328902	1366617	2430	0.071	2.430
328903	1366618	92	0.003	0.092
328904	1366619	697	0.020	0.697
328905	1366620	251	0.007	0.251
328906	1366621	286	0.008	0.286
328907	1366622	1345	0.039	1.345
328908	1366623	186	0.005	0.186
328909	1366624	180	0.005	0.180
328910	1366625	998	0.029	0.998
328911	1366626	601	0.018	0.601
328912 Dup	1366626	596	0.017	0.596
328913	1366627	28	<0.001	0.028
328914	1366628	16	<0.001	0.016
328915	1366629	101	0.003	0.101
328916	1366630	<5	<0.001	<0.005
328917	1366631	101	0.003	0.101
328918	1366632	41	0.001	0.041
328919	1366633	328	0.010	0.328
328920	1366634	877	0.026	0.877
328921	1366635	204	0.006	0.204
328922	1366636	162	0.005	0.162
328923 Dup	1366636	134	0.004	0.134
328924	1366637	222	0.006	0.222
328925	1366638	2182	0.064	2.182
328926	1366639	58	0.002	0.058
328927	1366640	2030	0.059	2.030
328928	1366641	64	0.002	0.064

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, December 13, 2012

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/04/2012
 Date Completed: 12/13/2012
 Job #: 201244518
 Reference: TL 12 281
 Sample #: 102

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
328929	1366642	70	0.002	0.070
328930	1366643	18	<0.001	0.018
328931	1366644	1783	0.052	1.783
328932	1366645	3301	0.096	3.301
328933	1366646	251	0.007	0.251
328934 Rep	1366646	246	0.007	0.246
328935	1366647	64	0.002	0.064
328936	1366648	89	0.003	0.089
328937	1366649	41	0.001	0.041
328938	1366650	<5	<0.001	<0.005
328939	1366651	29	<0.001	0.029
328940	1366652	52	0.002	0.052
328941	1366653	13	<0.001	0.013
328942	1366654	3509	0.102	3.509
328943	1366655	384	0.011	0.384
328944	1366656	671	0.020	0.671
328945 Dup	1366656	603	0.018	0.603
328946	1366657	885	0.026	0.885
328947	1366658	751	0.022	0.751
328948	1366659	291	0.008	0.291
328949	1366660	5145	0.150	5.145
328950	1366661	79	0.002	0.079
328951	1366662	84	0.002	0.084
328952	1366663	491	0.014	0.491
328953	1366664	2520	0.074	2.520
328954	1366665	105	0.003	0.105
328955	1366666	82	0.002	0.082
328956 Dup	1366666	88	0.003	0.088
328957	1366667	156	0.005	0.156
328958	1366668	1134	0.033	1.134

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, December 13, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/04/2012
 Date Completed: 12/13/2012
 Job #: 201244518
 Reference: TL 12 281
 Sample #: 102

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
328959	1366669	373	0.011	0.373
328960	1366670	<5	<0.001	<0.005
328961	1366671	409	0.012	0.409
328962	1366672	4781	0.139	4.781
328963	1366673	111	0.003	0.111
328964	1366674	42	0.001	0.042
328965	1366675	242	0.007	0.242
328966	1366676	373	0.011	0.373
328967 Dup	1366676	365	0.011	0.365
328968	1366677	1012	0.030	1.012
328969	1366678	198	0.006	0.198
328970	1366679	539	0.016	0.539
328971	1366680	229	0.007	0.229
328972	1366681	200	0.006	0.200
328973	1366682	328	0.010	0.328
328974	1366683	104	0.003	0.104
328975	1366684	347	0.010	0.347
328976	1366685	372	0.011	0.372
328977	1366686	464	0.014	0.464
328978 Dup	1366686	503	0.015	0.503
328979	1366687	495	0.014	0.495
328980	1366688	65	0.002	0.065

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Friday, December 21, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/05/2012
 Date Completed: 12/17/2012
 Job #: 201244542
 Reference: TL 12-283
 Sample #: 89

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
330353	1366689	1.931	2	7.07	30	678	<2	4	2.05	<4	10	42	22	2.08	0.04	21	1.11	905	8	55	491	60	1.55	<5	<5	<10	192	1785	<2	46	<10	9	312
330354	1366690	0.013	<1	3.20	6	383	<2	4	2.35	<4	17	54	24	3.38	0.07	7	1.39	683	3	41	609	2	0.22	<5	<5	<10	262	2598	<2	118	22	16	58
330355	1366691	0.807	9	3.77	12	558	<2	5	1.44	50	11	40	698	2.67	<0.01	8	0.70	609	9	75	409	3179	2.26	<5	<5	<10	171	1534	<2	37	170	6	15216
330356	1366692	0.054	1	4.09	19	522	<2	3	1.40	<4	11	33	65	1.90	<0.01	10	0.80	688	5	61	524	236	1.08	<5	<5	<10	164	1776	<2	41	10	6	553
330357	1366693	0.023	<1	3.53	10	495	<2	6	1.38	<4	9	63	20	1.84	<0.01	16	1.10	499	9	86	362	14	0.62	<5	<5	<10	140	1492	<2	37	<10	7	94
330358	1366694	0.015	<1	4.13	6	446	<2	9	0.74	<4	5	25	8	1.08	0.08	15	1.08	455	5	50	261	12	0.57	<5	<5	<10	118	935	<2	18	<10	5	134
330359	1366695	0.062	<1	3.92	11	539	<2	8	0.47	<4	5	39	20	1.10	<0.01	12	0.79	319	7	74	257	70	0.72	<5	<5	<10	95	958	<2	18	<10	5	407
330360	1366696	0.055	2	5.52	15	565	<2	6	0.69	<4	4	29	23	1.09	0.12	19	0.92	334	7	58	280	56	0.80	<5	<5	<10	122	1041	<2	19	12	6	611
330361	1366697	0.027	<1	4.65	14	503	<2	<1	1.02	<4	4	31	10	1.10	0.09	17	1.08	441	8	65	252	28	0.58	<5	<5	<10	141	973	<2	18	<10	5	132
330362	1366698	0.098	1	4.65	22	386	<2	11	0.86	<4	14	93	72	2.61	0.09	26	1.45	960	9	86	406	24	1.26	<5	<5	<10	113	1330	<2	56	<10	10	200
330363D	1366698	0.113	<1	6.17	24	427	<2	<1	0.99	<4	15	99	72	2.65	0.08	31	1.49	1043	10	87	416	26	1.34	<5	<5	<10	128	1423	<2	60	<10	11	194
330364	1366699	0.089	<1	5.21	7	383	<2	24	1.03	<4	13	85	103	2.32	0.13	21	1.29	1015	9	80	390	48	0.88	<5	<5	<10	108	1413	<2	52	<10	9	109
330365	1366700	2.104	1	3.55	2	400	<2	<1	2.27	<4	19	56	36	3.73	0.03	10	1.45	721	4	50	630	5	0.24	<5	<5	<10	252	2628	<2	123	24	17	61
330366	1366701	0.023	<1	2.36	7	363	<2	5	0.53	<4	6	37	14	1.24	<0.01	10	0.87	771	6	70	241	10	0.56	<5	<5	<10	72	982	<2	20	<10	4	55
330367	1366702	0.044	<1	4.26	5	386	<2	4	0.48	<4	4	27	24	0.98	<0.01	11	0.67	527	5	55	259	21	0.60	<5	<5	<10	81	1014	<2	19	<10	5	94
330368	1366703	0.130	<1	3.63	11	407	<2	7	0.32	<4	5	25	117	0.97	<0.01	11	0.57	371	5	55	238	7	0.69	<5	<5	<10	72	961	<2	17	11	4	548
330369	1366704	0.026	<1	3.38	6	438	<2	6	0.46	<4	5	28	18	1.05	0.02	7	0.73	524	5	53	270	3	0.56	<5	<5	<10	79	960	<2	19	<10	4	70
330370	1366705	0.064	2	5.22	7	386	<2	2	1.32	<4	19	105	48	3.15	0.03	25	1.62	747	10	84	479	15	0.92	<5	<5	<10	126	1783	<2	67	<10	10	101
330371	1366706	0.179	1	4.76	<2	521	<2	10	1.60	<4	19	103	57	3.19	0.03	15	1.13	557	9	88	474	29	1.07	<5	8	<10	189	2104	<2	67	<10	11	172
330372	1366707	0.046	<1	5.83	21	430	<2	9	1.04	<4	12	25	12	0.83	0.10	15	0.72	407	6	57	671	43	0.60	<5	<5	<10	109	2009	<2	38	<10	6	97

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Friday, December 21, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/05/2012
 Date Completed: 12/17/2012
 Job #: 201244542
 Reference: TL 12-283
 Sample #: 89

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
330373	1366708	0.034	<1	5.13	11	390	<2	2	1.60	<4	12	32	21	1.32	0.07	10	0.79	556	5	55	611	32	0.85	<5	<5	<10	103	1669	<2	34	<10	7	103
330374D	1366708	0.035	<1	4.97	8	391	<2	1	1.54	<4	12	33	21	1.28	0.07	10	0.78	540	6	53	585	28	0.82	<5	<5	<10	101	1668	<2	34	<10	6	100
330375	1366709	0.029	1	5.13	3	411	<2	<1	0.88	<4	10	24	10	1.00	0.06	11	0.84	490	7	54	605	23	0.49	<5	<5	<10	79	1776	<2	32	<10	6	76
330376	1366710	0.013	1	4.44	4	385	<2	2	2.40	<4	18	52	24	3.31	0.10	11	1.39	663	6	42	579	<1	0.29	<5	<5	<10	275	2738	<2	116	22	16	51
330377	1366711	0.018	2	3.49	4	386	<2	8	1.22	<4	7	19	10	1.16	<0.01	7	0.91	499	3	46	662	17	0.46	<5	<5	<10	95	1689	<2	30	<10	6	34
330378	1366712	0.025	1	4.82	<2	415	<2	3	2.35	<4	13	74	27	2.36	<0.01	14	1.33	979	7	77	383	23	0.98	<5	<5	<10	166	1583	<2	46	<10	9	100
330379	1366713	0.028	1	3.72	14	432	<2	<1	0.33	<4	32	23	15	1.26	<0.01	15	1.08	476	5	78	464	16	0.52	5	<5	<10	104	1149	<2	32	<10	5	46
330380	1366714	0.062	2	4.48	18	447	<2	5	0.50	<4	26	22	50	1.60	<0.01	20	1.11	533	6	65	465	1091	1.16	<5	<5	<10	124	1304	<2	30	<10	5	361
330381	1366715	0.185	3	3.82	23	551	<2	7	0.42	9	25	28	332	2.13	<0.01	14	0.77	421	6	77	434	1932	2.21	6	<5	<10	135	1243	<2	28	37	4	3164
330382	1366716	0.249	5	4.17	18	552	<2	5	0.48	7	24	35	198	1.95	<0.01	15	0.75	409	7	84	448	2044	1.96	7	<5	<10	147	1223	<2	28	31	4	2463
330383	1366717	0.048	<1	3.98	16	905	<2	6	0.41	<4	12	30	13	0.98	<0.01	13	0.67	298	6	65	443	283	0.86	<5	<5	<10	152	1313	<2	28	15	4	1222
330384	1366718	3.014	33	2.78	85	337	<2	8	1.08	60	21	38	2708	2.31	0.02	7	0.81	400	8	76	231	14818	3.79	102	<5	<10	133	785	<2	21	280	4	26043
330385D	1366718	3.317	35	3.38	89	307	<2	<1	1.17	62	21	38	2818	2.40	<0.01	9	0.85	411	9	77	242	14761	3.99	102	<5	<10	138	814	<2	21	289	5	25369
330386	1366719	0.864	3	4.31	32	326	<2	<1	0.32	9	15	42	138	1.46	0.05	13	0.55	238	8	77	358	2093	1.67	11	<5	<10	102	1038	<2	23	42	5	3254
330387	1366720	4.852	68	2.55	34	442	<2	6	1.30	20	15	34	53	2.91	0.04	6	0.85	487	6	37	511	569	0.55	44	<5	225	220	1767	<2	86	63	13	1834
330388	1366721	0.400	2	3.49	40	254	<2	11	0.59	9	28	33	60	1.34	0.08	15	1.05	610	8	84	427	1237	1.14	9	<5	<10	116	1052	<2	25	37	5	3068
330389	1366722	0.150	2	3.80	20	317	<2	<1	0.42	<4	24	35	10	0.87	<0.01	13	0.80	383	8	84	478	896	0.57	8	<5	<10	99	1090	<2	26	13	5	807
330390	1366723	0.068	<1	4.36	34	249	<2	12	0.98	<4	26	23	13	1.42	0.03	24	2.16	1145	8	64	497	133	0.62	<5	<5	<10	125	866	<2	28	<10	5	269
330391	1366724	0.087	<1	4.15	21	255	<2	4	0.28	<4	8	31	17	1.85	<0.01	16	1.59	902	9	70	408	217	1.02	<5	<5	<10	83	1097	<2	31	<10	5	599
330392	1366725	0.158	1	3.54	17	289	<2	8	0.57	<4	9	43	18	1.89	<0.01	13	1.24	843	9	75	473	38	0.95	5	<5	<10	80	1191	<2	33	<10	5	142

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Friday, December 21, 2012

Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 12/05/2012
 Date Completed: 12/17/2012
 Job #: 201244542
 Reference: TL 12-283
 Sample #: 89

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
330393	1366726	0.239	2	3.74	24	344	<2	<1	0.75	<4	8	28	10	1.70	<0.01	10	0.89	641	5	47	411	446	1.41	<5	<5	<10	86	1371	<2	29	10	5	733
330394	1366727	1.369	<1	4.60	38	639	<2	7	0.94	<4	7	43	14	1.53	0.06	15	0.83	623	7	59	408	358	1.38	5	<5	<10	84	1485	<2	29	14	5	880
330395	1366728	0.233	5	3.40	34	676	<2	9	0.90	7	7	35	128	1.86	<0.01	10	0.83	523	5	56	343	1266	1.82	6	<5	<10	69	1325	<2	26	30	6	2181
330396D	1366728	0.314	4	3.36	29	642	<2	<1	0.87	6	7	33	121	1.77	0.06	10	0.80	494	5	56	320	1186	1.76	<5	<5	<10	65	1247	<2	26	30	6	2078
330397	1366729	4.155	5	3.14	30	482	<2	3	0.47	7	8	33	389	1.75	0.04	10	0.74	496	4	57	380	1033	1.51	6	<5	<10	58	1299	<2	28	36	5	2601
330398	1366730	<0.005	<1	3.94	3	386	<2	1	2.37	<4	17	53	28	3.35	0.13	10	1.38	667	5	44	593	8	0.26	<5	<5	<10	270	2623	<2	117	21	16	74
330399	1366731	0.119	1	5.09	13	468	<2	8	0.43	<4	8	35	24	1.53	0.10	16	0.83	498	7	59	519	140	1.00	<5	<5	<10	78	1558	<2	37	<10	6	209
330400	1366732	0.188	2	3.09	29	236	<2	12	0.39	4	8	36	33	2.18	<0.01	10	1.13	637	5	54	434	575	1.73	<5	<5	<10	77	1261	<2	30	17	6	1261
330401	1366733	0.292	2	3.62	33	271	<2	<1	1.23	<4	10	44	20	2.23	<0.01	11	1.46	1093	7	62	435	489	1.55	<5	<5	<10	99	1509	<2	34	15	6	1035
330402	1366734	0.259	3	4.10	26	266	<2	<1	2.47	7	8	45	13	2.26	<0.01	10	1.51	1344	9	74	417	926	1.68	<5	<5	<10	113	1424	<2	34	32	6	2340
330403	1366735	1.526	4	3.18	63	242	<2	10	0.89	5	14	44	44	2.49	<0.01	7	0.73	557	6	69	628	811	2.46	<5	<5	<10	67	2053	<2	52	22	12	1466
330404	1366736	1.887	5	3.23	61	233	<2	2	0.90	5	14	42	41	2.55	<0.01	7	0.74	579	7	69	605	762	2.54	<5	<5	<10	70	2021	<2	51	19	12	1433
330405	1366737	0.882	7	3.59	52	283	<2	4	0.43	13	13	70	43	2.35	<0.01	9	0.61	420	7	77	425	2158	2.45	6	<5	<10	49	1599	<2	49	53	12	4144
330406	1366738	0.563	2	4.28	70	259	<2	6	1.01	<4	20	121	119	3.21	<0.01	13	0.93	867	8	95	442	345	2.67	<5	<5	<10	67	1831	<2	71	14	13	660
330407D	1366738	0.614	2	4.00	62	252	<2	5	0.98	<4	20	124	106	3.20	<0.01	12	0.92	870	9	107	434	305	2.62	<5	<5	<10	63	1819	<2	70	<10	13	592
330408	1366739	0.565	1	5.38	23	291	<2	5	1.74	<4	21	136	97	3.68	0.06	19	1.58	1284	10	100	462	109	1.82	<5	<5	<10	90	2263	<2	82	<10	15	381
330409	1366740	0.237	1	<0.01	396	>5000	<2	<1	0.85	<4	6	19	33	2.79	0.09	2	0.21	<100	15	26	<100	12	0.57	15	<5	<10	94	613	<2	15	44	7	23
330410	1366741	1.068	6	4.43	55	390	<2	<1	1.21	10	21	115	160	3.10	0.02	14	1.12	823	8	85	451	2136	2.43	9	<5	<10	71	1834	<2	62	49	13	3373
330411	1366742	0.196	2	5.31	33	419	<2	6	0.63	4	7	35	27	1.60	0.07	11	0.62	363	8	60	429	605	1.53	8	<5	<10	63	1568	<2	32	18	6	1383
330412	1366743	0.328	<1	4.18	27	344	<2	5	1.14	<4	7	41	35	1.61	0.08	10	0.83	614	5	59	409	56	1.19	6	<5	<10	74	1474	<2	33	<10	6	278

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Friday, December 21, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/05/2012
 Date Completed: 12/17/2012
 Job #: 201244542
 Reference: TL 12-283
 Sample #: 89

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
330413	1366744	0.197	<1	3.42	19	298	<2	<1	0.77	<4	7	27	30	1.54	<0.01	10	0.78	548	5	54	490	83	1.07	<5	<5	<10	76	1490	<2	30	<10	6	107
330414	1366745	0.059	<1	2.75	17	280	<2	10	1.43	<4	7	28	57	1.93	<0.01	11	1.33	1214	6	57	447	35	0.95	<5	<5	<10	89	1525	<2	31	<10	5	233
330415	1366746	0.101	3	3.49	14	234	<2	1	0.89	<4	7	34	38	1.68	<0.01	15	1.02	874	7	65	426	857	0.87	<5	<5	<10	99	1541	<2	30	15	5	940
330416	1366747	0.068	<1	2.61	12	293	<2	1	0.67	<4	7	24	15	1.49	<0.01	10	0.93	711	3	50	461	128	0.93	<5	<5	<10	74	1531	<2	29	<10	5	302
330417	1366748	0.126	2	3.56	27	433	<2	3	0.40	4	7	25	29	1.47	<0.01	13	0.59	260	5	54	435	754	1.51	<5	<5	<10	74	1386	<2	26	24	5	1588
330418R	1366748	0.098	1	2.71	53	374	<2	3	0.39	5	8	39	100	1.73	<0.01	9	0.60	292	5	66	449	666	1.47	<5	<5	<10	68	1176	<2	29	23	5	1702
330419	1366749	0.242	4	3.09	22	508	<2	5	0.50	8	7	29	72	1.83	<0.01	12	0.61	312	5	56	436	1850	1.91	<5	<5	<10	67	1367	<2	26	40	5	2982
330420	1366750	0.014	<1	1.72	<2	302	<2	3	2.04	<4	15	51	27	3.31	<0.01	5	1.31	637	3	43	565	13	0.18	<5	<5	<10	203	2345	<2	113	20	14	81
330421	1366751	0.044	<1	3.19	15	390	<2	2	1.46	<4	6	30	20	1.35	<0.01	10	1.27	830	5	54	362	134	0.65	<5	<5	<10	98	1354	<2	25	<10	4	139
330422	1366752	0.006	<1	2.04	<2	417	<2	5	0.61	<4	6	34	3	1.32	<0.01	13	1.06	302	8	68	308	2	0.20	<5	<5	<10	56	1357	<2	23	<10	4	32
330423	1366753	0.053	<1	3.85	10	421	<2	<1	2.47	<4	6	27	62	1.49	<0.01	16	1.56	626	6	55	301	181	0.53	<5	<5	<10	115	1224	<2	21	<10	4	513
330424	1366754	0.023	<1	2.94	3	393	<2	4	1.35	<4	6	26	6	1.31	<0.01	20	1.17	388	5	51	306	10	0.44	<5	<5	<10	92	1366	<2	22	<10	4	35
330425	1366755	0.256	1	2.28	16	314	<2	3	0.95	<4	7	23	16	1.43	<0.01	5	0.80	310	2	45	296	61	1.09	<5	<5	<10	74	1105	<2	21	<10	4	186
330426	1366756	0.332	2	4.42	11	382	<2	<1	0.86	<4	7	19	12	1.11	<0.01	12	0.72	239	6	40	269	56	0.91	<5	<5	<10	83	1274	<2	22	<10	5	107
330427	1366757	0.485	3	5.11	26	474	<2	5	0.43	<4	8	33	46	1.10	0.11	10	0.50	122	7	56	412	154	0.93	<5	<5	<10	83	1620	<2	33	<10	7	435
330428	1366758	0.022	<1	4.53	9	428	<2	<1	1.49	<4	7	23	11	1.20	0.12	13	0.85	248	4	43	337	16	0.52	<5	<5	<10	145	1403	<2	26	<10	6	43
330429D	1366758	0.023	<1	6.42	7	530	<2	<1	1.66	<4	8	22	11	1.22	<0.01	19	0.92	252	6	41	342	14	0.58	<5	<5	<10	163	1695	<2	30	<10	7	41
330430	1366759	0.078	<1	8.40	20	556	<2	44	1.98	<4	6	37	10	1.25	0.85	38	1.16	310	<1	66	355	35	0.46	<5	5	<10	124	1693	<2	32	<10	8	65
330431	1366760	1.903	<1	5.23	3	416	<2	8	2.27	<4	16	49	31	3.40	<0.01	14	1.35	655	6	42	559	3	0.32	<5	<5	<10	277	2745	<2	114	26	16	56
330432	1366761	1.851	2	6.11	28	497	<2	6	0.93	<4	7	33	31	1.32	0.06	17	0.77	264	9	55	376	42	1.22	8	<5	<10	82	1540	<2	32	16	7	935

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Friday, December 21, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 12/05/2012
 Date Completed: 12/17/2012
 Job #: 201244542
 Reference: TL 12-283
 Sample #: 89

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
330433	1366762	0.065	<1	9.00	21	580	<2	13	1.73	<4	10	32	29	1.46	0.19	29	1.28	392	13	60	400	48	1.00	<5	<5	<10	115	1688	<2	40	<10	9	99
330434	1366763	0.097	2	7.75	7	630	<2	8	1.52	<4	7	33	19	1.24	0.12	23	1.28	612	11	57	333	44	0.90	<5	<5	<10	105	1499	<2	27	<10	7	144
330435	1366764	0.023	<1	7.79	17	572	<2	<1	1.96	<4	6	27	8	1.29	0.17	21	1.42	524	10	48	323	36	0.71	6	<5	<10	102	1433	<2	25	<10	7	62
330436	1366765	0.338	2	5.91	4	558	<2	<1	0.89	<4	6	27	17	1.03	0.11	12	0.94	237	6	49	345	165	0.56	<5	<5	<10	64	1394	<2	25	12	6	463
330437	1366766	1.540	14	6.23	13	490	<2	4	0.89	<4	7	32	67	1.25	0.13	16	1.18	297	9	56	336	462	0.80	12	<5	<10	66	1235	<2	26	<10	6	413
330438	1366767	0.066	2	5.32	22	418	<2	<1	1.06	<4	7	32	14	1.14	0.09	13	0.94	281	8	51	283	36	0.75	<5	<5	<10	67	1190	<2	22	<10	5	92
330439	1366768	0.061	1	5.78	9	476	<2	7	1.19	<4	7	25	15	1.22	0.12	17	1.11	243	8	52	313	19	0.63	5	<5	<10	76	1379	<2	24	<10	6	52
330440D	1366768	0.048	<1	5.17	12	457	<2	7	1.16	<4	6	27	14	1.23	0.13	15	1.09	243	6	55	308	17	0.60	<5	<5	<10	75	1326	<2	23	<10	5	49
330441	1366769	0.092	<1	4.81	21	501	<2	3	0.73	<4	7	36	12	1.13	<0.01	12	0.83	216	7	71	329	10	0.59	<5	<5	<10	56	1435	<2	25	<10	5	38
330442	1366770	0.005	<1	3.78	2	367	<2	<1	2.27	<4	16	51	23	3.26	<0.01	10	1.32	639	4	41	561	<1	0.25	<5	<5	<10	262	2637	<2	113	20	15	48
330443	1366771	0.130	1	5.46	26	518	<2	2	1.16	<4	7	39	9	1.33	0.10	14	1.06	263	8	71	330	16	0.72	<5	<5	<10	70	1425	<2	26	<10	5	43
330444	1366772	0.036	<1	5.74	21	429	<2	11	1.06	<4	10	71	17	2.03	0.19	16	1.07	354	12	107	354	9	0.55	<5	<5	<10	77	1188	<2	51	<10	6	35
330445	1366773	0.082	<1	1.11	7	238	<2	<1	0.39	<4	4	10	4	0.66	<0.01	3	0.58	138	<1	25	180	3	0.41	<5	<5	<10	43	724	<2	14	<10	3	16
330446	1366774	0.180	1	5.61	24	419	<2	8	0.10	<4	7	24	18	0.91	0.14	13	0.50	<100	8	44	306	21	0.85	<5	<5	<10	65	1124	<2	25	<10	5	60
330447	1366775	0.172	2	<0.01	<2	122	<2	5	<0.01	<4	2	3	7	0.33	<0.01	<1	0.20	<100	<1	12	121	7	0.36	<5	<5	<10	32	440	<2	11	<10	2	14
330448	1366776	0.306	<1	7.09	23	469	<2	8	0.75	<4	7	25	24	1.16	0.13	23	0.71	112	12	50	379	22	1.17	5	<5	<10	107	1407	<2	34	<10	7	50
330449	1366777	0.019	<1	6.70	14	530	<2	2	2.42	<4	9	27	7	1.71	0.14	27	1.26	307	8	46	460	5	0.59	5	<5	<10	186	1836	<2	36	<10	7	47

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, December 17, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/05/2012
 Date Completed: 12/17/2012
 Job #: 201244542
 Reference: TL 12-283
 Sample #: 89

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
330353	1366689	1931	0.056	1.931
330354	1366690	13	<0.001	0.013
330355	1366691	807	0.024	0.807
330356	1366692	54	0.002	0.054
330357	1366693	23	<0.001	0.023
330358	1366694	15	<0.001	0.015
330359	1366695	62	0.002	0.062
330360	1366696	55	0.002	0.055
330361	1366697	27	<0.001	0.027
330362	1366698	98	0.003	0.098
330363 Dup	1366698	113	0.003	0.113
330364	1366699	89	0.003	0.089
330365	1366700	2104	0.061	2.104
330366	1366701	23	<0.001	0.023
330367	1366702	44	0.001	0.044
330368	1366703	130	0.004	0.130
330369	1366704	26	<0.001	0.026
330370	1366705	64	0.002	0.064
330371	1366706	179	0.005	0.179
330372	1366707	46	0.001	0.046
330373	1366708	34	<0.001	0.034
330374 Dup	1366708	35	0.001	0.035
330375	1366709	29	<0.001	0.029
330376	1366710	13	<0.001	0.013
330377	1366711	18	<0.001	0.018
330378	1366712	25	<0.001	0.025
330379	1366713	28	<0.001	0.028
330380	1366714	62	0.002	0.062
330381	1366715	185	0.005	0.185
330382	1366716	249	0.007	0.249

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, December 17, 2012

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/05/2012
 Date Completed: 12/17/2012
 Job #: 201244542
 Reference: TL 12-283
 Sample #: 89

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
330383	1366717	48	0.001	0.048
330384	1366718	3014	0.088	3.014
330385 Dup	1366718	3317	0.097	3.317
330386	1366719	864	0.025	0.864
330387	1366720	4852	0.142	4.852
330388	1366721	400	0.012	0.400
330389	1366722	150	0.004	0.150
330390	1366723	68	0.002	0.068
330391	1366724	87	0.003	0.087
330392	1366725	158	0.005	0.158
330393	1366726	239	0.007	0.239
330394	1366727	1369	0.040	1.369
330395	1366728	233	0.007	0.233
330396 Dup	1366728	314	0.009	0.314
330397	1366729	4155	0.121	4.155
330398	1366730	<5	<0.001	<0.005
330399	1366731	119	0.003	0.119
330400	1366732	188	0.005	0.188
330401	1366733	292	0.009	0.292
330402	1366734	259	0.008	0.259
330403	1366735	1526	0.045	1.526
330404	1366736	1887	0.055	1.887
330405	1366737	882	0.026	0.882
330406	1366738	563	0.016	0.563
330407 Dup	1366738	614	0.018	0.614
330408	1366739	565	0.016	0.565
330409	1366740	237	0.007	0.237
330410	1366741	1068	0.031	1.068
330411	1366742	196	0.006	0.196
330412	1366743	328	0.010	0.328

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, December 17, 2012

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/05/2012
 Date Completed: 12/17/2012
 Job #: 201244542
 Reference: TL 12-283
 Sample #: 89

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
330413	1366744	197	0.006	0.197
330414	1366745	59	0.002	0.059
330415	1366746	101	0.003	0.101
330416	1366747	68	0.002	0.068
330417	1366748	126	0.004	0.126
330418 Rep	1366748	98	0.003	0.098
330419	1366749	242	0.007	0.242
330420	1366750	14	<0.001	0.014
330421	1366751	44	0.001	0.044
330422	1366752	6	<0.001	0.006
330423	1366753	53	0.002	0.053
330424	1366754	23	<0.001	0.023
330425	1366755	256	0.007	0.256
330426	1366756	332	0.010	0.332
330427	1366757	485	0.014	0.485
330428	1366758	22	<0.001	0.022
330429 Dup	1366758	23	<0.001	0.023
330430	1366759	78	0.002	0.078
330431	1366760	1903	0.056	1.903
330432	1366761	1851	0.054	1.851
330433	1366762	65	0.002	0.065
330434	1366763	97	0.003	0.097
330435	1366764	23	<0.001	0.023
330436	1366765	338	0.010	0.338
330437	1366766	1540	0.045	1.540
330438	1366767	66	0.002	0.066
330439	1366768	61	0.002	0.061
330440 Dup	1366768	48	0.001	0.048
330441	1366769	92	0.003	0.092
330442	1366770	5	<0.001	0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, December 17, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/05/2012
 Date Completed: 12/17/2012
 Job #: 201244542
 Reference: TL 12-283
 Sample #: 89

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
330443	1366771	130	0.004	0.130
330444	1366772	36	0.001	0.036
330445	1366773	82	0.002	0.082
330446	1366774	180	0.005	0.180
330447	1366775	172	0.005	0.172
330448	1366776	306	0.009	0.306
330449	1366777	19	<0.001	0.019

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AlSu1


 Certified By: Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, December 20, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/07/2012
 Date Completed: 12/19/2012
 Job #: 201244559
 Reference: TL12-284
 Sample #: 92

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
331316	1366778	0.046	1	6.71	15	379	<2	22	1.67	<4	7	22	6	1.49	0.07	21	1.44	787	<1	35	387	77	1.36	<5	6	<10	180	1296	<2	31	<10	7	97
331317	1366779	0.034	1	4.80	10	388	<2	21	0.86	<4	6	27	5	0.68	0.03	16	0.89	504	<1	32	333	186	0.77	13	<5	<10	108	1265	<2	30	13	6	547
331318	1366780	5.158	68	4.59	35	463	<2	14	1.46	19	14	36	51	2.80	0.16	14	0.87	489	<1	29	522	588	0.91	66	<5	234	230	1795	<2	83	69	13	1842
331319	1366781	0.048	2	6.12	9	464	<2	8	1.22	<4	7	22	6	0.99	0.06	21	0.95	570	<1	31	375	46	1.08	<5	<5	<10	149	1521	<2	32	<10	6	96
331320	1366782	0.028	1	4.27	10	416	<2	15	0.93	<4	5	29	8	0.83	<0.01	13	0.66	408	<1	46	213	176	0.80	<5	6	<10	114	1216	2	31	10	5	500
331321	1366783	0.027	<1	4.81	8	515	<2	5	1.06	<4	8	35	11	0.85	<0.01	14	0.66	453	<1	45	193	43	0.88	<5	<5	<10	129	1304	<2	35	<10	6	61
331322	1366784	0.405	2	4.94	13	473	<2	7	0.56	5	6	27	156	0.55	0.05	10	0.39	216	<1	42	236	542	0.90	13	<5	<10	121	1248	<2	28	21	5	1649
331323	1366785	0.214	1	6.90	17	564	<2	15	2.73	<4	11	34	26	1.84	0.09	22	1.60	1246	<1	48	461	187	1.44	9	<5	<10	235	1726	<2	38	<10	7	247
331324	1366786	0.024	1	4.98	13	572	<2	22	1.74	<4	8	45	13	1.90	<0.01	18	0.83	611	<1	69	440	30	0.98	<5	6	<10	185	1752	<2	38	<10	7	84
331325	1366787	0.083	1	5.59	21	506	<2	12	1.36	<4	8	36	67	1.85	0.02	18	0.59	468	<1	51	440	207	1.82	<5	6	<10	186	1715	<2	37	10	7	394
331326D	1366787	0.104	1	6.19	23	524	<2	16	1.47	<4	9	37	68	1.84	0.12	19	0.60	465	<1	54	435	217	1.84	<5	<5	<10	202	1727	<2	37	10	8	393
331327	1366788	0.038	<1	5.08	13	607	<2	17	1.56	<4	9	45	14	1.72	0.09	14	0.66	545	<1	67	437	35	1.22	9	<5	<10	179	1704	<2	36	<10	7	68
331328	1366789	0.036	1	4.91	10	545	<2	22	1.67	<4	9	39	11	1.76	0.11	16	0.71	562	<1	56	440	44	1.37	<5	<5	<10	158	1808	<2	35	<10	7	109
331329	1366790	0.006	<1	4.12	5	336	<2	15	2.20	<4	15	53	22	3.08	0.03	13	1.29	628	<1	33	562	5	0.51	<5	<5	<10	225	2419	4	106	20	15	48
331330	1366791	0.031	1	4.78	11	443	<2	24	1.60	<4	7	47	19	1.94	0.09	21	0.97	733	<1	60	466	107	1.07	<5	<5	<10	149	1594	<2	37	<10	7	273
331331	1366792	0.016	<1	4.81	10	543	<2	22	2.92	<4	6	76	10	1.74	0.09	17	0.83	629	1	92	423	25	1.03	<5	10	<10	380	1444	<2	40	<10	8	68
331332	1366793	0.030	1	5.82	14	438	<2	18	2.10	<4	14	101	18	2.13	0.05	23	1.37	545	<1	81	551	22	1.25	10	<5	<10	214	1843	<2	54	10	8	55
331333	1366794	0.383	2	4.92	31	442	<2	22	0.55	<4	8	66	44	1.39	<0.01	17	0.63	220	<1	76	347	378	1.45	<5	<5	<10	96	1191	<2	31	<10	5	559
331334	1366795	0.058	2	5.05	9	305	<2	12	1.18	<4	17	140	43	3.12	0.12	23	1.33	624	<1	89	442	35	1.40	<5	<5	<10	134	1848	<2	66	<10	12	82
331335	1366796	0.059	2	5.46	4	319	<2	18	1.26	<4	17	141	44	3.23	0.06	25	1.42	646	<1	94	462	39	1.41	<5	<5	<10	143	1924	2	68	<10	12	80

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By:  Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, December 20, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/07/2012
 Date Completed: 12/19/2012
 Job #: 201244559
 Reference: TL12-284
 Sample #: 92

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
331336	1366797	0.131	1	5.56	16	407	<2	20	1.39	<4	16	116	62	2.90	0.12	21	1.11	574	<1	73	466	45	1.63	<5	<5	<10	159	1794	<2	65	<10	11	424
331337D	1366797	0.160	1	5.01	18	377	<2	11	1.29	<4	16	110	60	2.81	0.13	19	1.05	547	<1	72	446	45	1.56	5	<5	<10	147	1664	<2	60	<10	10	412
331338	1366798	0.164	6	5.58	36	517	<2	21	1.06	7	14	85	104	2.75	0.12	19	0.71	411	<1	71	409	1067	2.71	5	<5	<10	147	1759	<2	51	33	10	1853
331339	1366799	0.028	2	5.99	7	507	<2	26	1.49	<4	6	58	50	1.74	0.14	18	0.74	401	<1	86	390	84	1.26	<5	7	<10	169	1404	2	37	<10	8	102
331340	1366800	0.235	1	0.50	394	>5000	<2	21	0.92	<4	6	21	31	2.74	0.07	5	0.19	<100	5	18	<100	21	0.79	21	<5	<10	77	427	7	14	49	7	22
331341	1366801	0.020	1	2.64	16	447	<2	12	0.57	<4	6	33	14	1.17	0.05	12	0.58	259	<1	39	366	25	1.06	<5	<5	<10	75	1146	<2	26	<10	6	48
331342	1366802	0.043	1	4.30	17	287	<2	16	0.96	<4	6	22	17	0.84	<0.01	12	0.62	342	<1	38	566	26	0.79	5	<5	<10	98	1412	<2	26	<10	6	93
331343	1366803	0.320	5	4.35	41	322	<2	19	0.23	<4	7	26	21	1.18	<0.01	9	0.42	167	<1	50	553	117	1.48	8	<5	<10	53	1464	<2	29	11	6	536
331344	1366804	0.346	2	4.85	49	335	<2	18	0.13	<4	6	60	10	1.52	<0.01	9	0.36	<100	3	101	505	45	1.82	<5	8	<10	50	1342	<2	30	<10	6	143
331345	1366805	0.140	1	5.90	19	332	<2	8	1.38	<4	6	25	16	1.53	0.03	17	0.88	465	<1	34	577	27	1.37	<5	<5	<10	90	1709	<2	32	11	7	37
331346	1366806	0.110	1	4.56	21	360	<2	11	1.29	<4	3	31	8	1.18	0.03	12	0.78	425	<1	30	445	51	1.02	<5	<5	<10	92	1274	<2	26	<10	6	77
331347	1366807	0.013	1	4.81	2	394	<2	27	1.45	<4	4	42	5	1.18	0.09	17	1.08	675	<1	43	670	28	0.61	7	<5	<10	101	1581	<2	29	<10	7	60
331348D	1366807	0.010	<1	5.19	7	389	<2	19	1.50	<4	4	43	6	1.19	0.06	19	1.11	689	<1	48	683	29	0.68	8	<5	<10	103	1576	<2	30	<10	7	65
331349	1366808	0.010	1	6.91	2	354	3	17	3.60	<4	7	29	9	1.59	0.19	24	1.86	1354	<1	47	572	37	0.71	7	<5	<10	162	1670	<2	33	27	9	154
331350	1366809	0.048	1	5.63	<2	350	<2	17	1.16	<4	14	110	42	2.31	0.10	23	1.34	763	3	71	449	37	1.19	<5	<5	<10	106	1786	<2	54	10	11	76
331351	1366810	0.006	<1	4.45	6	342	<2	23	2.18	<4	15	52	22	2.98	0.02	14	1.28	607	<1	32	558	3	0.54	<5	<5	<10	233	2306	<2	104	21	15	49
331352	1366811	1.386	1	4.90	20	314	<2	24	0.86	<4	18	135	61	3.27	<0.01	24	1.67	915	<1	96	480	93	1.59	<5	<5	<10	105	1558	3	72	<10	9	110
331353	1366812	0.225	2	4.79	25	305	<2	18	0.68	<4	9	72	146	2.51	<0.01	23	1.32	769	<1	68	377	585	1.84	<5	<5	<10	94	1153	4	45	<10	7	712
331354	1366813	2.422	2	5.26	29	262	<2	21	0.92	<4	15	117	23	3.02	<0.01	39	2.20	1220	<1	87	482	485	1.46	<5	<5	<10	117	1418	<2	64	<10	8	255
331355	1366814	0.597	4	4.95	19	257	<2	15	0.78	4	10	58	23	2.31	0.13	36	2.22	1014	<1	48	453	1995	1.22	<5	<5	<10	95	1023	4	44	16	6	1047

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, December 20, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/07/2012
 Date Completed: 12/19/2012
 Job #: 201244559
 Reference: TL12-284
 Sample #: 92

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
331356	1366815	0.366	2	6.60	21	251	<2	22	0.95	<4	4	46	9	1.33	0.11	35	1.81	743	<1	73	426	602	1.09	<5	<5	<10	105	671	<2	26	<10	6	269
331357	1366816	0.486	2	4.65	18	204	<2	27	0.63	<4	2	23	7	1.10	0.10	28	1.65	642	<1	32	367	530	0.93	<5	<5	<10	82	571	3	21	<10	5	324
331358	1366817	0.380	3	6.56	19	321	<2	11	0.61	<4	2	34	5	1.06	0.08	20	1.04	358	<1	53	472	1566	1.26	5	<5	<10	82	852	<2	26	24	6	1138
331359D	1366817	0.353	3	6.07	18	307	<2	10	0.56	<4	3	31	5	1.04	0.05	18	1.00	344	<1	49	477	1565	1.24	<5	<5	<10	77	810	<2	26	21	6	1149
331360	1366818	1.261	2	5.18	9	282	<2	13	0.43	<4	4	27	9	0.81	0.12	15	0.66	232	<1	42	441	689	1.05	7	<5	<10	68	831	<2	24	19	5	1277
331361	1366819	0.189	3	5.67	17	253	<2	38	0.67	<4	4	27	10	1.03	0.15	23	1.62	647	<1	46	477	274	0.93	6	<5	<10	84	723	2	24	11	6	433
331362	1366820	2.223	1	4.02	7	362	<2	20	2.14	<4	17	54	35	3.34	0.05	14	1.37	668	<1	37	595	9	0.46	<5	<5	<10	217	2342	<2	110	24	15	61
331363	1366821	2.529	<1	3.41	23	140	<2	21	0.51	<4	8	24	6	1.20	<0.01	25	2.18	1034	<1	44	384	77	0.59	9	<5	<10	73	583	<2	20	<10	4	133
331364	1366822	1.292	1	4.70	19	223	<2	10	0.59	<4	5	31	7	1.21	0.06	24	1.48	748	<1	55	438	231	0.94	<5	<5	<10	85	823	<2	24	15	5	712
331365	1366823	0.225	2	5.10	17	217	<2	<1	1.04	<4	5	39	29	1.86	0.06	26	1.78	892	<1	48	536	322	1.31	7	5	<10	92	931	<2	30	14	7	743
331366	1366824	0.147	<1	5.40	17	314	<2	19	0.89	<4	4	30	36	1.82	0.10	25	1.71	827	<1	45	531	63	1.29	6	7	<10	98	935	<2	30	10	6	472
331367	1366825	0.291	1	6.42	27	302	<2	23	0.79	<4	5	24	10	1.98	0.05	27	1.83	1005	<1	37	416	321	1.54	8	<5	<10	96	1075	4	28	18	6	1008
331368	1366826	0.149	1	6.58	20	318	<2	11	0.90	<4	3	25	8	1.65	0.18	23	1.52	949	<1	42	401	114	1.44	<5	<5	<10	104	1169	<2	27	<10	6	206
331369	1366827	0.167	1	7.22	16	431	<2	27	1.76	<4	6	37	12	1.59	0.14	27	1.60	1188	<1	65	392	77	1.43	<5	5	<10	139	1406	2	27	14	7	678
331370D	1366827	0.196	1	6.72	19	426	<2	16	1.71	<4	4	36	12	1.58	0.20	25	1.57	1175	<1	70	382	81	1.37	7	<5	<10	134	1413	4	27	13	6	672
331371	1366828	0.357	3	6.05	13	762	<2	17	1.76	<4	4	25	8	1.28	0.11	21	1.34	954	<1	42	415	1134	1.09	12	<5	<10	122	1533	<2	27	13	6	426
331372	1366829	0.036	1	5.60	10	503	<2	19	1.09	<4	4	29	9	1.39	0.09	21	0.72	471	<1	48	436	40	1.05	9	<5	<10	103	1543	2	27	<10	6	37
331373	1366830	0.005	<1	5.79	8	397	<2	16	2.45	<4	16	55	23	3.17	0.25	17	1.34	655	<1	35	573	4	0.64	<5	10	<10	272	2656	<2	111	24	16	48
331374	1366831	0.040	1	6.42	13	411	<2	17	1.31	<4	5	23	10	1.54	0.14	20	0.70	511	<1	42	388	15	1.25	6	8	<10	126	1500	<2	28	<10	7	33
331375	1366832	0.027	1	5.81	13	393	<2	42	1.16	<4	4	36	10	1.58	0.04	19	0.73	434	<1	66	425	11	1.14	7	<5	<10	116	1508	<2	26	<10	7	28

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, December 20, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/07/2012
 Date Completed: 12/19/2012
 Job #: 201244559
 Reference: TL12-284
 Sample #: 92

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
331376	1366833	0.033	2	7.74	8	358	<2	12	2.04	<4	9	64	23	2.34	0.08	24	1.20	966	<1	57	454	30	1.68	7	<5	<10	162	1897	<2	45	<10	11	63
331377	1366834	0.101	2	6.60	5	408	<2	10	1.45	<4	18	108	48	3.33	0.14	26	1.38	913	<1	86	557	22	1.70	<5	<5	<10	124	2135	<2	73	<10	13	79
331378	1366835	0.054	1	6.89	4	257	<2	15	2.58	<4	18	105	34	3.08	0.06	26	1.65	1199	<1	73	530	30	1.08	<5	7	<10	150	3022	4	82	<10	12	100
331379	1366836	0.053	2	6.19	11	251	<2	27	2.42	<4	19	106	35	3.05	0.06	24	1.62	1131	<1	66	528	28	1.00	7	<5	<10	145	3047	4	82	<10	11	107
331380	1366837	0.859	9	5.90	37	332	<2	18	0.98	<4	18	126	150	3.10	0.08	20	1.06	802	<1	94	471	727	2.51	5	<5	<10	90	1650	<2	75	16	12	781
331381R	1366837	0.816	7	3.64	29	216	<2	20	0.73	<4	15	94	114	2.37	<0.01	12	0.82	564	<1	67	365	523	1.91	<5	<5	<10	73	1147	<2	53	13	9	730
331382	1366838	0.308	<1	2.12	16	119	<2	35	0.91	<4	9	67	56	1.93	<0.01	5	0.75	511	<1	55	267	44	1.45	<5	<5	<10	59	809	<2	32	<10	8	108
331383	1366839	0.669	1	2.77	25	143	<2	20	0.94	<4	12	95	40	2.33	<0.01	11	0.99	626	<1	66	340	23	1.51	<5	<5	<10	69	1108	<2	45	<10	9	52
331384	1366840	4.511	56	2.18	29	291	<2	17	1.03	16	11	33	42	2.19	<0.01	8	0.71	392	<1	27	419	490	0.72	44	<5	180	144	1317	<2	64	53	10	1516
331385	1366841	0.621	2	3.39	15	159	<2	15	1.10	<4	13	114	61	2.63	<0.01	16	1.28	792	<1	75	412	44	1.39	<5	<5	<10	74	1257	<2	50	<10	9	114
331386	1366842	0.142	1	3.81	18	241	<2	26	1.29	<4	7	42	49	1.49	<0.01	14	0.90	604	<1	50	386	155	1.17	6	<5	<10	80	1154	<2	27	13	6	638
331387	1366843	0.143	2	3.58	26	222	<2	20	0.86	<4	4	26	11	1.19	<0.01	11	0.70	380	<1	39	378	990	1.37	<5	<5	<10	62	862	<2	19	15	5	916
331388	1366844	0.048	1	4.03	17	233	<2	8	0.59	<4	5	17	6	0.91	<0.01	12	0.54	231	<1	25	417	253	1.29	<5	<5	<10	57	922	<2	18	16	6	1013
331389	1366845	0.171	1	3.98	18	226	<2	20	1.31	<4	9	23	40	1.43	<0.01	11	0.83	548	<1	35	417	100	1.26	5	<5	<10	79	1103	<2	21	<10	5	133
331390	1366846	0.045	<1	4.08	17	232	<2	16	1.45	<4	7	23	17	1.19	<0.01	16	0.83	565	<1	40	415	37	1.20	5	<5	<10	84	1061	<2	18	<10	6	98
331391	1366847	0.463	3	3.35	20	253	<2	21	0.76	4	4	25	28	1.12	<0.01	11	0.64	346	<1	35	350	943	1.31	<5	<5	<10	60	1062	<2	20	21	5	1372
331392D	1366847	0.529	3	3.09	17	215	<2	15	0.73	<4	3	24	27	1.05	<0.01	10	0.59	316	<1	37	332	903	1.29	13	<5	<10	58	929	<2	17	21	5	1310
331393	1366848	0.123	<1	3.03	21	239	<2	20	0.93	<4	6	55	8	1.47	<0.01	12	0.71	453	<1	87	384	56	1.14	<5	<5	<10	59	1029	<2	21	<10	5	128
331394	1366849	0.052	<1	4.25	8	327	<2	19	1.55	<4	3	20	14	0.91	<0.01	16	1.03	419	<1	34	248	42	0.74	8	<5	<10	77	998	<2	15	<10	4	70
331395	1366850	<0.005	<1	1.88	<2	211	<2	17	1.46	<4	11	41	17	2.26	<0.01	6	0.98	451	<1	26	428	4	0.35	<5	<5	<10	147	1725	<2	77	20	11	34

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, December 20, 2012


Final Certificate

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/07/2012
 Date Completed: 12/19/2012
 Job #: 201244559
 Reference: TL12-284
 Sample #: 92

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
331396	1366851	0.493	3	3.12	8	249	<2	10	1.27	<4	3	20	54	0.82	<0.01	12	0.90	363	<1	33	244	329	0.81	<5	<5	<10	62	873	<2	13	17	4	1134
331397	1366852	0.137	2	2.15	15	255	<2	6	0.37	<4	3	20	12	0.73	<0.01	6	0.43	107	<1	37	272	130	0.83	<5	<5	<10	43	795	<2	12	<10	4	179
331398	1366853	0.162	<1	3.53	7	286	<2	22	1.15	<4	2	25	6	0.86	<0.01	12	0.81	213	<1	41	281	29	0.68	<5	<5	<10	67	975	<2	15	<10	4	158
331399	1366854	12.896	41	2.82	48	238	<2	16	0.11	<4	3	35	81	1.28	<0.01	9	0.31	<100	<1	56	285	495	1.62	29	<5	<10	39	825	<2	16	14	5	617
331400	1366855	0.073	1	3.93	24	318	<2	13	0.55	<4	4	24	8	0.94	<0.01	12	0.56	180	<1	40	297	30	1.09	<5	6	<10	53	1078	<2	20	<10	5	41
331401	1366856	0.103	<1	4.07	28	301	<2	23	0.51	<4	3	24	7	0.90	<0.01	12	0.55	171	<1	39	300	30	1.10	8	9	<10	52	1111	<2	22	<10	5	37
331402	1366857	0.212	2	3.56	21	237	<2	26	1.07	<4	4	25	24	1.08	<0.01	15	0.96	330	<1	41	270	123	1.06	<5	<5	<10	70	942	<2	18	<10	5	154
331403D	1366857	0.157	2	3.56	22	255	<2	9	1.02	<4	4	27	23	1.06	<0.01	15	0.94	323	<1	40	259	113	1.00	5	<5	<10	70	985	<2	19	<10	5	151
331404	1366858	0.134	1	4.23	15	285	<2	33	1.04	<4	5	19	8	0.84	<0.01	16	0.90	231	<1	30	278	36	0.76	<5	<5	<10	73	999	<2	16	<10	5	75
331405	1366859	0.091	<1	2.57	5	213	<2	18	0.85	<4	3	25	6	0.85	<0.01	11	0.86	191	<1	42	252	43	0.53	6	<5	<10	55	812	<2	13	<10	4	42
331406	1366860	0.232	<1	0.22	328	>5000	<2	18	0.74	<4	7	19	25	2.24	<0.01	3	0.18	<100	3	14	<100	12	0.80	20	<5	<10	84	356	<2	11	43	5	13
331407	1366861	0.044	<1	3.41	9	355	<2	6	0.73	<4	5	23	9	0.84	<0.01	11	0.69	156	<1	37	283	11	0.64	<5	<5	<10	55	884	<2	15	<10	5	31
331408	1366862	0.029	1	4.27	14	292	<2	10	1.08	<4	4	19	15	0.88	<0.01	14	0.82	196	<1	29	263	18	0.84	8	<5	<10	62	939	<2	16	<10	5	77
331409	1366863	0.017	1	4.72	11	270	<2	5	0.98	<4	4	19	15	0.81	<0.01	16	0.81	232	<1	26	291	11	0.84	7	<5	<10	75	966	<2	16	<10	6	28
331410	1366864	0.051	<1	3.61	17	293	<2	15	0.18	<4	3	16	14	0.75	<0.01	9	0.43	<100	<1	26	307	5	1.00	<5	5	<10	47	909	<2	15	<10	5	19
331411	1366865	0.022	<1	3.69	11	285	<2	15	0.26	<4	3	14	8	0.61	<0.01	11	0.50	<100	<1	17	291	10	0.86	<5	<5	<10	57	765	<2	14	<10	5	19
331412	1366866	0.334	1	4.02	19	298	<2	21	0.20	<4	3	15	16	0.70	<0.01	12	0.48	<100	<1	19	276	18	1.03	<5	<5	<10	59	718	<2	14	<10	5	63
331413	1366867	2.586	4	4.12	20	259	<2	10	0.46	<4	4	21	78	0.91	<0.01	15	0.54	<100	<1	24	312	355	1.38	<5	11	<10	67	761	<2	22	12	7	723
331414D	1366867	2.164	3	4.25	24	253	<2	31	0.47	<4	3	21	78	0.92	<0.01	16	0.55	<100	<1	22	313	363	1.42	6	<5	<10	67	769	<2	22	15	7	728
331415	1366868	0.199	2	3.46	21	234	<2	30	0.24	<4	4	17	35	0.76	<0.01	14	0.44	<100	<1	21	474	310	1.04	8	<5	<10	61	850	<2	21	<10	6	357

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Jason Moore, General Manager

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, December 20, 2012


Final Certificate

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 12/07/2012
 Date Completed: 12/19/2012
 Job #: 201244559
 Reference: TL12-284
 Sample #: 92

Acc #	Client ID	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	Li ppm	Mg %	Mn ppm	Mo ppm	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Se ppm	Sn ppm	Sr ppm	Ti ppm	Tl ppm	V ppm	W ppm	Y ppm	Zn ppm
331416	1366869	0.066	<1	4.97	9	242	<2	16	1.94	<4	6	18	6	1.35	<0.01	18	0.96	233	<1	21	422	46	0.86	12	10	<10	176	1254	<2	25	<10	6	75

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Jason Moore, General Manager

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Wednesday, December 19, 2012

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/07/2012
 Date Completed: 12/19/2012
 Job #: 201244559
 Reference: TL12-284
 Sample #: 92

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
331316	1366778	46	0.001	0.046
331317	1366779	34	<0.001	0.034
331318	1366780	5158	0.150	5.158
331319	1366781	48	0.001	0.048
331320	1366782	28	<0.001	0.028
331321	1366783	27	<0.001	0.027
331322	1366784	405	0.012	0.405
331323	1366785	214	0.006	0.214
331324	1366786	24	<0.001	0.024
331325	1366787	83	0.002	0.083
331326 Dup	1366787	104	0.003	0.104
331327	1366788	38	0.001	0.038
331328	1366789	36	0.001	0.036
331329	1366790	6	<0.001	0.006
331330	1366791	31	<0.001	0.031
331331	1366792	16	<0.001	0.016
331332	1366793	30	<0.001	0.030
331333	1366794	383	0.011	0.383
331334	1366795	58	0.002	0.058
331335	1366796	59	0.002	0.059
331336	1366797	131	0.004	0.131
331337 Dup	1366797	160	0.005	0.160
331338	1366798	164	0.005	0.164
331339	1366799	28	<0.001	0.028
331340	1366800	235	0.007	0.235
331341	1366801	20	<0.001	0.020
331342	1366802	43	0.001	0.043
331343	1366803	320	0.009	0.320
331344	1366804	346	0.010	0.346
331345	1366805	140	0.004	0.140

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Wednesday, December 19, 2012


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/07/2012
 Date Completed: 12/19/2012
 Job #: 201244559
 Reference: TL12-284
 Sample #: 92

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
331346	1366806	110	0.003	0.110
331347	1366807	13	<0.001	0.013
331348 Dup	1366807	10	<0.001	0.010
331349	1366808	10	<0.001	0.010
331350	1366809	48	0.001	0.048
331351	1366810	6	<0.001	0.006
331352	1366811	1386	0.040	1.386
331353	1366812	225	0.007	0.225
331354	1366813	2422	0.071	2.422
331355	1366814	597	0.017	0.597
331356	1366815	366	0.011	0.366
331357	1366816	486	0.014	0.486
331358	1366817	380	0.011	0.380
331359 Dup	1366817	353	0.010	0.353
331360	1366818	1261	0.037	1.261
331361	1366819	189	0.006	0.189
331362	1366820	2223	0.065	2.223
331363	1366821	2529	0.074	2.529
331364	1366822	1292	0.038	1.292
331365	1366823	225	0.007	0.225
331366	1366824	147	0.004	0.147
331367	1366825	291	0.009	0.291
331368	1366826	149	0.004	0.149
331369	1366827	167	0.005	0.167
331370 Dup	1366827	196	0.006	0.196
331371	1366828	357	0.010	0.357
331372	1366829	36	0.001	0.036
331373	1366830	5	<0.001	0.005
331374	1366831	40	0.001	0.040
331375	1366832	27	<0.001	0.027

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Wednesday, December 19, 2012

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/07/2012
 Date Completed: 12/19/2012
 Job #: 201244559
 Reference: TL12-284
 Sample #: 92

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
331376	1366833	33	<0.001	0.033
331377	1366834	101	0.003	0.101
331378	1366835	54	0.002	0.054
331379	1366836	53	0.002	0.053
331380	1366837	859	0.025	0.859
331381 Rep	1366837	816	0.024	0.816
331382	1366838	308	0.009	0.308
331383	1366839	669	0.020	0.669
331384	1366840	4511	0.132	4.511
331385	1366841	621	0.018	0.621
331386	1366842	142	0.004	0.142
331387	1366843	143	0.004	0.143
331388	1366844	48	0.001	0.048
331389	1366845	171	0.005	0.171
331390	1366846	45	0.001	0.045
331391	1366847	463	0.013	0.463
331392 Dup	1366847	529	0.015	0.529
331393	1366848	123	0.004	0.123
331394	1366849	52	0.002	0.052
331395	1366850	<5	<0.001	<0.005
331396	1366851	493	0.014	0.493
331397	1366852	137	0.004	0.137
331398	1366853	162	0.005	0.162
331399	1366854	12896	0.376	12.896
331400	1366855	73	0.002	0.073
331401	1366856	103	0.003	0.103
331402	1366857	212	0.006	0.212
331403 Dup	1366857	157	0.005	0.157
331404	1366858	134	0.004	0.134
331405	1366859	91	0.003	0.091

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Wednesday, December 19, 2012


Preliminary Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 12/07/2012
 Date Completed: 12/19/2012
 Job #: 201244559
 Reference: TL12-284
 Sample #: 92

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
331406	1366860	232	0.007	0.232
331407	1366861	44	0.001	0.044
331408	1366862	29	<0.001	0.029
331409	1366863	17	<0.001	0.017
331410	1366864	51	0.001	0.051
331411	1366865	22	<0.001	0.022
331412	1366866	334	0.010	0.334
331413	1366867	2586	0.075	2.586
331414 Dup	1366867	2164	0.063	2.164
331415	1366868	199	0.006	0.199
331416	1366869	66	0.002	0.066

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.

The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, January 21, 2013

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/24/2012
 Date Completed: 01/21/2013
 Job #: 201244709
 Reference: TL12 285
 Sample #: 116

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
346867	1366983	39	0.001	0.039
346868	1366984	699	0.020	0.699
346869	1366985	207	0.006	0.207
346870	1366986	22	<0.001	0.022
346871	1366987	13	<0.001	0.013
346872	1366988	29	<0.001	0.029
346873	1366989	122	0.004	0.122
346874	1366990	10	<0.001	0.010
346875	1366991	18	<0.001	0.018
346876	1366992	14	<0.001	0.014
346877 Dup	1366992	14	<0.001	0.014
346878	1366993	14	<0.001	0.014
346879	1366994	89	0.003	0.089
346880	1366995	37	0.001	0.037
346881	1366996	43	0.001	0.043
346882	1366997	15	<0.001	0.015
346883	1366998	71	0.002	0.071
346884	1366999	32	<0.001	0.032
346885	1367000	2264	0.066	2.264
346886	1367401	31	<0.001	0.031
346887	1367402	119	0.003	0.119
346888 Dup	1367402	131	0.004	0.131
346889	1367403	154	0.004	0.154
346890	1367404	89	0.003	0.089
346891	1367405	81	0.002	0.081
346892	1367406	44	0.001	0.044
346893	1367407	<5	<0.001	<0.005
346894	1367408	<5	<0.001	<0.005
346895	1367409	<5	<0.001	<0.005
346896	1367410	11	<0.001	0.011

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, January 21, 2013

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/24/2012
 Date Completed: 01/21/2013
 Job #: 201244709
 Reference: TL12 285
 Sample #: 116

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
346897	1367411	385	0.011	0.385
346898	1367412	83	0.002	0.083
346899 Dup	1367412	61	0.002	0.061
346900	1367413	<5	<0.001	<0.005
346901	1367414	5	<0.001	0.005
346902	1367415	<5	<0.001	<0.005
346903	1367416	5	<0.001	0.005
346904	1367417	69	0.002	0.069
346905	1367418	791	0.023	0.791
346906	1367419	180	0.005	0.180
346907	1367420	3855	0.112	3.855
346908	1367421	497	0.014	0.497
346909	1367422	800	0.023	0.800
346910 Dup	1367422	807	0.024	0.807
346911	1367423	674	0.020	0.674
346912	1367424	325	0.009	0.325
346913	1367425	172	0.005	0.172
346914	1367426	434	0.013	0.434
346915	1367427	280	0.008	0.280
346916	1367428	155	0.005	0.155
346917	1367429	114	0.003	0.114
346918	1367430	<5	<0.001	<0.005
346919	1367431	293	0.009	0.293
346920	1367432	854	0.025	0.854
346921 Dup	1367432	875	0.026	0.875
346922	1367433	895	0.026	0.895
346923	1367434	238	0.007	0.238
346924	1367435	187	0.005	0.187
346925	1367436	125	0.004	0.125
346926	1367437	368	0.011	0.368

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, January 21, 2013


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/24/2012
 Date Completed: 01/21/2013
 Job #: 201244709
 Reference: TL12 285
 Sample #: 116

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
346927	1367438	297	0.009	0.297
346928	1367439	313	0.009	0.313
346929	1367440	269	0.008	0.269
346930	1367441	3335	0.097	3.335
346931	1367442	376	0.011	0.376
346932 Rep	1367442	379	0.011	0.379
346933	1367443	1363	0.040	1.363
346934	1367444	67	0.002	0.067
346935	1367445	77	0.002	0.077
346936	1367446	57	0.002	0.057
346937	1367447	41	0.001	0.041
346938	1367448	170	0.005	0.170
346939	1367449	3769	0.110	3.769
346940	1367450	11	<0.001	0.011
346941	1367451	625	0.018	0.625
346942	1367452	556	0.016	0.556
346943 Dup	1367452	553	0.016	0.553
346944	1367453	877	0.026	0.877
346945	1367454	210	0.006	0.210
346946	1367455	861	0.025	0.861
346947	1367456	342	0.010	0.342
346948	1367457	482	0.014	0.482
346949	1367458	143	0.004	0.143
346950	1367459	102	0.003	0.102
346951	1367460	2066	0.060	2.066
346952	1367461	36	0.001	0.036
346953	1367462	43	0.001	0.043
346954 Dup	1367462	30	<0.001	0.030
346955	1367463	81	0.002	0.081
346956	1367464	96	0.003	0.096

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, January 21, 2013

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/24/2012
 Date Completed: 01/21/2013
 Job #: 201244709
 Reference: TL12 285
 Sample #: 116

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
346957	1367465	172	0.005	0.172
346958	1367466	844	0.025	0.844
346959	1367467	80	0.002	0.080
346960	1367468	43	0.001	0.043
346961	1367469	145	0.004	0.145
346962	1367470	<5	<0.001	<0.005
346963	1367471	121	0.004	0.121
346964	1367472	92	0.003	0.092
346965 Dup	1367472	131	0.004	0.131
346966	1367473	727	0.021	0.727
346967	1367474	23	<0.001	0.023
346968	1367475	22	<0.001	0.022
346969	1367476	146	0.004	0.146
346970	1367477	33	<0.001	0.033
346971	1367478	51	0.001	0.051
346972	1367479	40	0.001	0.040
346973	1367480	5320	0.155	5.320
346974	1367481	868	0.025	0.868
346975	1367482	32	<0.001	0.032
346976 Dup	1367482	25	<0.001	0.025
346977	1367483	974	0.028	0.974
346978	1367484	3435	0.100	3.435
346979	1367485	79	0.002	0.079
346980	1367486	29	<0.001	0.029
346981	1367487	16	<0.001	0.016
346982	1367488	227	0.007	0.227
346983	1367489	82	0.002	0.082
346984	1367490	7	<0.001	0.007
346985	1367491	51	0.001	0.051
346986	1367492	143	0.004	0.143

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, January 21, 2013


Preliminary Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 12/24/2012
 Date Completed: 01/21/2013
 Job #: 201244709
 Reference: TL12 285
 Sample #: 116

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
346987 Dup	1367492	149	0.004	0.149
346988	1367493	48	0.001	0.048
346989	1367494	45	0.001	0.045
346990	1367495	91	0.003	0.091
346991	1367496	118	0.003	0.118
346992	1367497	64	0.002	0.064
346993	1367498	219	0.006	0.219

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AlSu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Wednesday, January 16, 2013

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/19/2012
 Date Completed: 01/16/2013
 Job #: 201244674
 Reference: TL 286-12RE
 Sample #: 64

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
345334	1370885	263	0.008	0.263
345335	1370886	502	0.015	0.502
345336	1370887	16	<0.001	0.016
345337	1370888	15	<0.001	0.015
345338	1370889	14	<0.001	0.014
345339	1370890	245	0.007	0.245
345340	1370891	11	<0.001	0.011
345341	1370892	48	0.001	0.048
345342	1370893	<5	<0.001	<0.005
345343	1370894	25	<0.001	0.025
345344 Dup	1370894	18	<0.001	0.018
345345	1370895	9	<0.001	0.009
345346	1370896	6	<0.001	0.006
345347	1370897	12	<0.001	0.012
345348	1370898	11	<0.001	0.011
345349	1370899	340	0.010	0.340
345350	1370900	<5	<0.001	<0.005
345351	1370901	237	0.007	0.237
345352	1370902	1271	0.037	1.271
345353	1370903	1404	0.041	1.404
345354	1370904	363	0.011	0.363
345355 Dup	1370904	460	0.013	0.460
345356	1370905	62	0.002	0.062
345357	1370906	70	0.002	0.070
345358	1370907	142	0.004	0.142
345359	1370908	1298	0.038	1.298
345360	1370909	335	0.010	0.335
345361	1370910	1988	0.058	1.988
345362	1370911	1810	0.053	1.810
345363	1370912	384	0.011	0.384

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Wednesday, January 16, 2013

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/19/2012
 Date Completed: 01/16/2013
 Job #: 201244674
 Reference: TL 286-12RE
 Sample #: 64

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
345364	1370913	969	0.028	0.969
345365	1370914	68	0.002	0.068
345366 Dup	1370914	68	0.002	0.068
345367	1370915	276	0.008	0.276
345368	1370916	163	0.005	0.163
345369	1370917	110	0.003	0.110
345370	1370918	44	0.001	0.044
345371	1370919	32	<0.001	0.032
345372	1370920	6	<0.001	0.006
345373	1370921	62	0.002	0.062
345374	1370922	122	0.004	0.122
345375	1370923	79	0.002	0.079
345376	1370924	60	0.002	0.060
345377 Dup	1370924	60	0.002	0.060
345378	1370925	131	0.004	0.131
345379	1370926	444	0.013	0.444
345380	1370927	351	0.010	0.351
345381	1370928	208	0.006	0.208
345382	1370929	134	0.004	0.134
345383	1370930	5210	0.152	5.210
345384	1370931	200	0.006	0.200
345385	1370932	430	0.013	0.430
345386	1370933	308	0.009	0.308
345387	1370934	1193	0.035	1.193
345388 Dup	1370934	1345	0.039	1.345
345389	1370935	113	0.003	0.113
345390	1370936	44	0.001	0.044
345391	1370937	15	<0.001	0.015
345392	1370938	38	0.001	0.038
345393	1370939	11	<0.001	0.011

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Wednesday, January 16, 2013


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/19/2012
 Date Completed: 01/16/2013
 Job #: 201244674
 Reference: TL 286-12RE
 Sample #: 64

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
345394	1370940	<5	<0.001	<0.005
345395	1370941	543	0.016	0.543
345396	1370942	86	0.003	0.086
345397	1370943	90	0.003	0.090
345398	1370944	6	<0.001	0.006
345399 Rep	1370944	<5	<0.001	<0.005
345400	1370945	<5	<0.001	<0.005
345401	1370946	<5	<0.001	<0.005
345402	1370947	530	0.015	0.530
345403	1370948	15	<0.001	0.015

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Wednesday, January 23, 2013

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/28/2012
 Date Completed: 01/23/2013
 Job #: 201244713
 Reference: TL12-287
 Sample #: 116

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
347007	1367499	69	0.002	0.069
347008	1367500	237	0.007	0.237
347009	1367501	466	0.014	0.466
347010	1367502	6	<0.001	0.006
347011	1367503	70	0.002	0.070
347012	1367504	22	<0.001	0.022
347013	1367505	22	<0.001	0.022
347014	1367506	2042	0.060	2.042
347015	1367507	18	<0.001	0.018
347016	1367508	21975	0.641	21.975
347017 Dup	1367508	21627	0.631	21.627
347018	1367509	51	0.001	0.051
347019	1367510	<5	<0.001	<0.005
347020	1367511	48	0.001	0.048
347021	1367512	87	0.003	0.087
347022	1367513	85	0.002	0.085
347023	1367514	316	0.009	0.316
347024	1367515	101	0.003	0.101
347025	1367516	125	0.004	0.125
347026	1367517	102	0.003	0.102
347027	1367518	207	0.006	0.207
347028 Dup	1367518	137	0.004	0.137
347029	1367519	164	0.005	0.164
347030	1367520	2052	0.060	2.052
347031	1367521	106	0.003	0.106
347032	1367522	107	0.003	0.107
347033	1367523	19	<0.001	0.019
347034	1367524	46	0.001	0.046
347035	1367525	22	<0.001	0.022
347036	1367526	29	<0.001	0.029

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Wednesday, January 23, 2013

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/28/2012
 Date Completed: 01/23/2013
 Job #: 201244713
 Reference: TL12-287
 Sample #: 116

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
347037	1367527	28	<0.001	0.028
347038	1367528	102	0.003	0.102
347039 Dup	1367528	81	0.002	0.081
347040	1367529	23	<0.001	0.023
347041	1367530	8	<0.001	0.008
347042	1367531	11	<0.001	0.011
347043	1367532	13	<0.001	0.013
347044	1367533	73	0.002	0.073
347045	1367534	89	0.003	0.089
347046	1367535	29	<0.001	0.029
347047	1367536	36	0.001	0.036
347048	1367537	5	<0.001	0.005
347049	1367538	<5	<0.001	<0.005
347050 Dup	1367538	<5	<0.001	<0.005
347051	1367539	<5	<0.001	<0.005
347052	1367540	Insufficient Sample		
347053	1367541	147	0.004	0.147
347054	1367542	99	0.003	0.099
347055	1367543	296	0.009	0.296
347056	1367544	314	0.009	0.314
347057	1367545	508	0.015	0.508
347058	1367546	709	0.021	0.709
347059	1367547	249	0.007	0.249
347060	1367548	128	0.004	0.128
347061 Dup	1367548	119	0.003	0.119
347062	1367549	594	0.017	0.594
347063	1367550	<5	<0.001	<0.005
347064	1367551	150	0.004	0.150
347065	1367552	191	0.006	0.191
347066	1367553	80	0.002	0.080

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Wednesday, January 23, 2013

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/28/2012
 Date Completed: 01/23/2013
 Job #: 201244713
 Reference: TL12-287
 Sample #: 116

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
347067	1367554	271	0.008	0.271
347068	1367555	378	0.011	0.378
347069	1367556	324	0.009	0.324
347070	1367557	385	0.011	0.385
347071	1367558	207	0.006	0.207
347072 Rep	1367558	303	0.009	0.303
347073	1367559	3567	0.104	3.567
347074	1367560	250	0.007	0.250
347075	1367561	1033	0.030	1.033
347076	1367562	897	0.026	0.897
347077	1367563	3418	0.100	3.418
347078	1367564	1705	0.050	1.705
347079	1367565	92	0.003	0.092
347080	1367566	23	<0.001	0.023
347081	1367567	87	0.003	0.087
347082	1367568	90	0.003	0.090
347083 Dup	1367568	171	0.005	0.171
347084	1367569	138	0.004	0.138
347085	1367570	<5	<0.001	<0.005
347086	1367571	360	0.010	0.360
347087	1367572	355	0.010	0.355
347088	1367573	408	0.012	0.408
347089	1367574	1013	0.030	1.013
347090	1367575	421	0.012	0.421
347091	1367576	803	0.023	0.803
347092	1367577	54	0.002	0.054
347093	1367578	21	<0.001	0.021
347094 Dup	1367578	24	<0.001	0.024
347095	1367579	23	<0.001	0.023
347096	1367580	2157	0.063	2.157

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Wednesday, January 23, 2013


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 12/28/2012
 Date Completed: 01/23/2013
 Job #: 201244713
 Reference: TL12-287
 Sample #: 116

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
347097	1367581	115	0.003	0.115
347098	1367582	184	0.005	0.184
347099	1367583	61	0.002	0.061
347100	1367584	635	0.019	0.635
347101	1367585	104	0.003	0.104
347102	1367586	54	0.002	0.054
347103	1367587	63	0.002	0.063
347104	1367588	102	0.003	0.102
347105 Dup	1367588	98	0.003	0.098
347106	1367589	270	0.008	0.270
347107	1367590	8	<0.001	0.008
347108	1367591	402	0.012	0.402
347109	1367592	185	0.005	0.185
347110	1367593	116	0.003	0.116
347111	1367594	24	<0.001	0.024
347112	1367595	50	0.001	0.050
347113	1367596	28	<0.001	0.028
347114	1367597	711	0.021	0.711
347115	1367598	39	0.001	0.039
347116 Dup	1367598	42	0.001	0.042
347117	1367599	38	0.001	0.038
347118	1367600	5257	0.153	5.257
347119	1367601	777	0.023	0.777
347120	1367602	152	0.004	0.152
347121	1367603	46	0.001	0.046
347122	1367604	35	0.001	0.035
347123	1367605	314	0.009	0.314
347124	1367606	83	0.002	0.083
347125	1367607	21	<0.001	0.021
347126	1367608	36	0.001	0.036

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Wednesday, January 23, 2013


Preliminary Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 12/28/2012
 Date Completed: 01/23/2013
 Job #: 201244713
 Reference: TL12-287
 Sample #: 116

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
347127 Dup	1367608	31	<0.001	0.031
347128	1367609	77	0.002	0.077
347129	1367610	11	<0.001	0.011
347130	1367611	68	0.002	0.068
347131	1367612	150	0.004	0.150
347132	1367613	424	0.012	0.424
347133	1367614	31	<0.001	0.031

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, January 22, 2013


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 01/04/2013
 Date Completed: 01/22/2013
 Job #: 201340007
 Reference: TL12-288
 Sample #: 36

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
684	1368519	94	0.003	0.094
685	1368520	<5	<0.001	<0.005
686	1368521	6	<0.001	0.006
687	1368522	23	<0.001	0.023
688	1368523	8	<0.001	0.008
689	1368524	20	<0.001	0.020
690	1368525	30	<0.001	0.030
691	1368526	47	0.001	0.047
692	1368527	707	0.021	0.707
693	1368528	32	<0.001	0.032
694 Dup	1368528	24	<0.001	0.024
695	1368529	346	0.010	0.346
696	1368530	1813	0.053	1.813
697	1368531	1106	0.032	1.106
698	1368532	23	<0.001	0.023
699	1368533	317	0.009	0.317
700	1368534	806	0.024	0.806
701	1368535	132	0.004	0.132
702	1368536	281	0.008	0.281
703	1368537	49	0.001	0.049
704	1368538	159	0.005	0.159
705 Dup	1368538	227	0.007	0.227
706	1368539	154	0.005	0.154
707	1368540	<5	<0.001	<0.005
708	1368541	373	0.011	0.373
709	1368542	204	0.006	0.204
710	1368543	307	0.009	0.307
711	1368544	166	0.005	0.166
712	1368545	266	0.008	0.266
713	1368546	187	0.005	0.187

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, January 22, 2013


Preliminary Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 01/04/2013
 Date Completed: 01/22/2013
 Job #: 201340007
 Reference: TL12-288
 Sample #: 36

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
714	1368547	100	0.003	0.100
715	1368548	108	0.003	0.108
716 Dup	1368548	124	0.004	0.124
717	1368549	349	0.010	0.349
718	1368550	4835	0.141	4.835
719	1368551	63	0.002	0.063
720	1368552	963	0.028	0.963
721	1368553	165	0.005	0.165
722	1368554	20	<0.001	0.020

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, January 24, 2013


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 01/07/2013
 Date Completed: 01/24/2013
 Job #: 201340042
 Reference: TL12-289
 Sample #: 65

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
3367	1367665	10	<0.001	0.010
3368	1367666	8	<0.001	0.008
3369	1367667	11	<0.001	0.011
3370	1367668	13	<0.001	0.013
3371	1367669	10	<0.001	0.010
3372	1367670	<5	<0.001	<0.005
3373	1367671	40	0.001	0.040
3374	1367672	21	<0.001	0.021
3375	1367673	11	<0.001	0.011
3376	1367674	9	<0.001	0.009
3377 Dup	1367674	16	<0.001	0.016
3378	1367675	13	<0.001	0.013
3379	1367676	17	<0.001	0.017
3380	1367677	15	<0.001	0.015
3381	1367678	13	<0.001	0.013
3382	1367679	14	<0.001	0.014
3383	1367680	229	0.007	0.229
3384	1367681	39	0.001	0.039
3385	1367682	51	0.001	0.051
3386	1367683	31	<0.001	0.031
3387	1367684	24	<0.001	0.024
3388 Dup	1367684	24	<0.001	0.024
3389	1367685	26	<0.001	0.026
3390	1367686	20	<0.001	0.020
3391	1367687	76	0.002	0.076
3392	1367688	85	0.002	0.085
3393	1367689	24	<0.001	0.024
3394	1367690	9	<0.001	0.009
3395	1367691	44	0.001	0.044
3396	1367692	19	<0.001	0.019

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, January 24, 2013

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 01/07/2013
 Date Completed: 01/24/2013
 Job #: 201340042
 Reference: TL12-289
 Sample #: 65

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
3397	1367693	17	<0.001	0.017
3398	1367694	19	<0.001	0.019
3399 Dup	1367694	20	<0.001	0.020
3400	1367695	19	<0.001	0.019
3401	1367696	16	<0.001	0.016
3402	1367697	295	0.009	0.295
3403	1367698	1907	0.056	1.907
3404	1367699	1773	0.052	1.773
3405	1367700	2157	0.063	2.157
3406	1367701	592	0.017	0.592
3407	1367702	231	0.007	0.231
3408	1367703	33	<0.001	0.033
3409	1367704	53	0.002	0.053
3410 Dup	1367704	52	0.002	0.052
3411	1367705	136	0.004	0.136
3412	1367706	54	0.002	0.054
3413	1367707	83	0.002	0.083
3414	1367708	187	0.005	0.187
3415	1367709	859	0.025	0.859
3416	1367710	14	<0.001	0.014
3417	1367711	202	0.006	0.202
3418	1367712	811	0.024	0.811
3419	1367713	199	0.006	0.199
3420	1367714	50	0.001	0.050
3421 Dup	1367714	46	0.001	0.046
3422	1367715	320	0.009	0.320
3423	1367716	57	0.002	0.057
3424	1367717	201	0.006	0.201
3425	1367718	64	0.002	0.064
3426	1367719	150	0.004	0.150

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, January 24, 2013


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 01/07/2013
 Date Completed: 01/24/2013
 Job #: 201340042
 Reference: TL12-289
 Sample #: 65

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
3427	1367720	5388	0.157	5.388
3428	1367721	536	0.016	0.536
3429	1367722	1462	0.043	1.462
3430	1367723	569	0.017	0.569
3431	1367724	72	0.002	0.072
3432 Rep	1367724	97	0.003	0.097
3433	1367725	830	0.024	0.830
3434	1367726	81	0.002	0.081
3435	1367727	214	0.006	0.214
3436	1367728	49	0.001	0.049
3437	1367729	14	<0.001	0.014

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, January 24, 2013


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 01/04/2013
 Date Completed: 01/24/2013
 Job #: 201340010
 Reference: TL12-290
 Sample #: 77

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
858	1368555	118	0.003	0.118
859	1368556	98	0.003	0.098
860	1368557	97	0.003	0.097
861	1368558	130	0.004	0.130
862	1368559	119	0.003	0.119
863	1368560	<5	<0.001	<0.005
864	1368561	60	0.002	0.060
865	1368562	46	0.001	0.046
866	1368563	18	<0.001	0.018
867	1368564	28	<0.001	0.028
868 Dup	1368564	27	<0.001	0.027
869	1368565	<5	<0.001	<0.005
870	1368566	<5	<0.001	<0.005
871	1368567	10	<0.001	0.010
872	1368568	<5	<0.001	<0.005
873	1368569	<5	<0.001	<0.005
874	1368570	226	0.007	0.226
875	1368571	63	0.002	0.063
876	1368572	48	0.001	0.048
877	1368573	79	0.002	0.079
878	1368574	41	0.001	0.041
879 Dup	1368574	43	0.001	0.043
880	1368575	122	0.004	0.122
881	1368576	410	0.012	0.410
882	1368577	27	<0.001	0.027
883	1368578	1762	0.051	1.762
884	1368579	69	0.002	0.069
885	1368580	<5	<0.001	<0.005
886	1368581	44	0.001	0.044
887	1368582	893	0.026	0.893

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, January 24, 2013


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 01/04/2013
 Date Completed: 01/24/2013
 Job #: 201340010
 Reference: TL12-290
 Sample #: 77

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
888	1368583	27	<0.001	0.027
889	1368584	34	<0.001	0.034
890 Dup	1368584	57	0.002	0.057
891	1368585	45	0.001	0.045
892	1368586	60	0.002	0.060
893	1368587	38	0.001	0.038
894	1368588	90	0.003	0.090
895	1368589	111	0.003	0.111
896	1368590	2098	0.061	2.098
897	1368591	216	0.006	0.216
898	1368592	72	0.002	0.072
899	1368593	421	0.012	0.421
900	1368594	103	0.003	0.103
901 Dup	1368594	77	0.002	0.077
902	1368595	1847	0.054	1.847
903	1368596	16180	0.472	16.180
904	1368597	101	0.003	0.101
905	1368598	91	0.003	0.091
906	1368599	114	0.003	0.114
907	1368600	<5	<0.001	<0.005
908	1368601	202	0.006	0.202
909	1368602	120	0.003	0.120
910	1368603	548	0.016	0.548
911	1368604	162	0.005	0.162
912 Dup	1368604	141	0.004	0.141
913	1368605	57	0.002	0.057
914	1368606	59	0.002	0.059
915	1368607	87	0.003	0.087
916	1368608	15	<0.001	0.015
917	1368609	1558	0.045	1.558

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, January 24, 2013

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 01/04/2013
 Date Completed: 01/24/2013
 Job #: 201340010
 Reference: TL12-290
 Sample #: 77

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
918	1368610	5269	0.154	5.269
919	1368611	193	0.006	0.193
920	1368612	29	<0.001	0.029
921	1368613	111	0.003	0.111
922	1368614	84	0.002	0.084
923 Rep	1368614	25	<0.001	0.025
924	1368615	80	0.002	0.080
925	1368616	37	0.001	0.037
926	1368617	38	0.001	0.038
927	1368618	53	0.002	0.053
928	1368619	93	0.003	0.093
929	1368620	57	0.002	0.057
930	1368621	127	0.004	0.127
931	1368622	103	0.003	0.103
932	1368623	260	0.008	0.260
933	1368624	38	0.001	0.038
934 Dup	1368624	31	<0.001	0.031
935	1368625	403	0.012	0.403
936	1368626	331	0.010	0.331
937	1368627	225	0.007	0.225
938	1368628	30	<0.001	0.030
939	1368629	137	0.004	0.137
940	1368630	248	0.007	0.248
941	1368631	66	0.002	0.066

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AlSu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Friday, February 1, 2013


Final Certificate

Treasury Metals Inc
Exchange Tower 130 King St Suite 3680
Toronto, On, CAN
M5X 1B1
Ph#: (416) 599-4133
Fax#: (416) 599-4959
Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 01/24/2013
Date Completed: 02/01/2013
Job #: 201340191
Reference: TL 12-290
Sample #: 1

Acc #	Client ID	Au Grav oz/t	Au Grav g/t(ppm)
14922	1368596	0.308	10.541

PROCEDURE CODES: ALFA7

Certified By: 
Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, January 22, 2013


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 01/04/2013
 Date Completed: 01/22/2013
 Job #: 201340008
 Reference: TL12-291
 Sample #: 73

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
723	1367730	7	<0.001	0.007
724	1367731	365	0.011	0.365
725	1367732	68	0.002	0.068
726	1367733	53	0.002	0.053
727	1367734	61	0.002	0.061
728	1367735	138	0.004	0.138
729	1367736	93	0.003	0.093
730	1367737	93	0.003	0.093
731	1367738	135	0.004	0.135
732	1367739	508	0.015	0.508
733 Dup	1367739	421	0.012	0.421
734	1367740	236	0.007	0.236
735	1367741	101	0.003	0.101
736	1367742	92	0.003	0.092
737	1367743	29	<0.001	0.029
738	1367744	49	0.001	0.049
739	1367745	77	0.002	0.077
740	1367746	134	0.004	0.134
741	1367747	512	0.015	0.512
742	1367748	584	0.017	0.584
743	1367749	148	0.004	0.148
744 Dup	1367749	92	0.003	0.092
745	1367750	7	<0.001	0.007
746	1367751	117	0.003	0.117
747	1367752	58	0.002	0.058
748	1367753	63	0.002	0.063
749	1367754	196	0.006	0.196
750	1367755	192	0.006	0.192
751	1367756	169	0.005	0.169
752	1367757	116	0.003	0.116

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, January 22, 2013

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 01/04/2013
 Date Completed: 01/22/2013
 Job #: 201340008
 Reference: TL12-291
 Sample #: 73

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
753	1367758	85	0.002	0.085
754	1367759	62	0.002	0.062
755 Dup	1367759	52	0.002	0.052
756	1367760	2036	0.059	2.036
757	1367761	61	0.002	0.061
758	1367762	328	0.010	0.328
759	1367763	247	0.007	0.247
760	1367764	1089	0.032	1.089
761	1367765	37	0.001	0.037
762	1367766	71	0.002	0.071
763	1367767	60	0.002	0.060
764	1367768	99	0.003	0.099
765	1367769	58	0.002	0.058
766 Dup	1367769	87	0.003	0.087
767	1367770	<5	<0.001	<0.005
768	1367771	31	<0.001	0.031
769	1367772	179	0.005	0.179
770	1367773	201	0.006	0.201
771	1367774	119	0.003	0.119
772	1367775	59	0.002	0.059
773	1367776	33	<0.001	0.033
774	1367777	35	0.001	0.035
775	1367778	34	<0.001	0.034
776	1367779	68	0.002	0.068
777 Dup	1367779	78	0.002	0.078
778	1367780	4596	0.134	4.596
779	1367781	51	0.001	0.051
780	1367782	9	<0.001	0.009
781	1367783	37	0.001	0.037
782	1367784	66	0.002	0.066

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Tuesday, January 22, 2013


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 01/04/2013
 Date Completed: 01/22/2013
 Job #: 201340008
 Reference: TL12-291
 Sample #: 73

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
783	1367785	6	<0.001	0.006
784	1367786	42	0.001	0.042
785	1367787	69	0.002	0.069
786	1367788	75	0.002	0.075
787	1367789	56	0.002	0.056
788 Rep	1367789	58	0.002	0.058
789	1367790	<5	<0.001	<0.005
790	1367791	89	0.003	0.089
791	1367792	20	<0.001	0.020
792	1367793	54	0.002	0.054
793	1367794	61	0.002	0.061
794	1367795	27	<0.001	0.027
795	1367796	30	<0.001	0.030
796	1367797	154	0.004	0.154
797	1367798	17	<0.001	0.017
798	1367799	45	0.001	0.045
799 Dup	1367799	34	<0.001	0.034
800	1367800	269	0.008	0.269
801	1367801	156	0.005	0.156
802	1367802	19	<0.001	0.019

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, January 24, 2013

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 01/07/2013
 Date Completed: 01/24/2013
 Job #: 201340044
 Reference: TL12-292
 Sample #: 89

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
3500	1367803	10	<0.001	0.010
3501	1367804	25	<0.001	0.025
3502	1367805	<5	<0.001	<0.005
3503	1367806	<5	<0.001	<0.005
3504	1367807	8	<0.001	0.008
3505	1367808	5	<0.001	0.005
3506	1367809	77	0.002	0.077
3507	1367810	<5	<0.001	<0.005
3508	1367811	5	<0.001	0.005
3509	1367812	<5	<0.001	<0.005
3510 Dup	1367812	6	<0.001	0.006
3511	1367813	<5	<0.001	<0.005
3512	1367814	9	<0.001	0.009
3513	1367815	104	0.003	0.104
3514	1367816	50	0.001	0.050
3515	1367817	13	<0.001	0.013
3516	1367818	20	<0.001	0.020
3517	1367819	46	0.001	0.046
3518	1367820	2166	0.063	2.166
3519	1367821	57	0.002	0.057
3520	1367822	104	0.003	0.104
3521 Dup	1367822	72	0.002	0.072
3522	1367823	16	<0.001	0.016
3523	1367824	222	0.006	0.222
3524	1367825	513	0.015	0.513
3525	1367826	38	0.001	0.038
3526	1367827	39	0.001	0.039
3527	1367828	19	<0.001	0.019
3528	1367829	22	<0.001	0.022
3529	1367830	11	<0.001	0.011

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

 Certified By: 
 Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, January 24, 2013

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 01/07/2013
 Date Completed: 01/24/2013
 Job #: 201340044
 Reference: TL12-292
 Sample #: 89

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
3530	1367831	320	0.009	0.320
3531	1367832	63	0.002	0.063
3532 Dup	1367832	54	0.002	0.054
3533	1367833	398	0.012	0.398
3534	1367834	561	0.016	0.561
3535	1367835	764	0.022	0.764
3536	1367836	285	0.008	0.285
3537	1367837	54	0.002	0.054
3538	1367838	121	0.004	0.121
3539	1367839	416	0.012	0.416
3540	1367840	5115	0.149	5.115
3541	1367841	375	0.011	0.375
3542	1367842	943	0.028	0.943
3543 Dup	1367842	971	0.028	0.971
3544	1367843	366	0.011	0.366
3545	1367844	148	0.004	0.148
3546	1367845	144	0.004	0.144
3547	1367846	41	0.001	0.041
3548	1367847	24	<0.001	0.024
3549	1367848	837	0.024	0.837
3550	1367849	1125	0.033	1.125
3551	1367850	6	<0.001	0.006
3552	1367851	177	0.005	0.177
3553	1367852	193	0.006	0.193
3554 Dup	1367852	225	0.007	0.225
3555	1367853	3279	0.096	3.279
3556	1367854	383	0.011	0.383
3557	1367855	786	0.023	0.786
3558	1367856	1235	0.036	1.235
3559	1367857	64	0.002	0.064

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, January 24, 2013

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 01/07/2013
 Date Completed: 01/24/2013
 Job #: 201340044
 Reference: TL12-292
 Sample #: 89

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
3560	1367858	19	<0.001	0.019
3561	1367859	12	<0.001	0.012
3562	1367860	240	0.007	0.240
3563	1367861	9	<0.001	0.009
3564	1367862	12	<0.001	0.012
3565 Rep	1367862	8	<0.001	0.008
3566	1367863	17	<0.001	0.017
3567	1367864	83	0.002	0.083
3568	1367865	189	0.006	0.189
3569	1367866	204	0.006	0.204
3570	1367867	54	0.002	0.054
3571	1367868	30	<0.001	0.030
3572	1367869	67	0.002	0.067
3573	1367870	<5	<0.001	<0.005
3574	1367871	33	<0.001	0.033
3575	1367872	43	0.001	0.043
3576 Dup	1367872	40	0.001	0.040
3577	1367873	26	<0.001	0.026
3578	1367874	187	0.005	0.187
3579	1367875	302	0.009	0.302
3580	1367876	194	0.006	0.194
3581	1367877	119	0.003	0.119
3582	1367878	108	0.003	0.108
3583	1367879	423	0.012	0.423
3584	1367880	2047	0.060	2.047
3585	1367881	561	0.016	0.561
3586	1367882	174	0.005	0.174
3587 Dup	1367882	164	0.005	0.164
3588	1367883	66	0.002	0.066
3589	1367884	9	<0.001	0.009

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, January 24, 2013


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 01/07/2013
 Date Completed: 01/24/2013
 Job #: 201340044
 Reference: TL12-292
 Sample #: 89

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
3590	1367885	9	<0.001	0.009
3591	1367886	77	0.002	0.077
3592	1367887	42	0.001	0.042
3593	1367888	177	0.005	0.177
3594	1367889	193	0.006	0.193
3595	1367890	<5	<0.001	<0.005
3596	1367891	36	0.001	0.036

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AlSu1

 Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Wednesday, January 23, 2013


Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 01/04/2013
 Date Completed: 01/23/2013
 Job #: 201340005
 Reference: TL12-293
 Sample #: 41

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
538	1368632	192	0.006	0.192
539	1368633	314	0.009	0.314
540	1368634	159	0.005	0.159
541	1368635	112	0.003	0.112
542	1368636	82	0.002	0.082
543	1368637	92	0.003	0.092
544	1368638	166	0.005	0.166
545	1368639	79	0.002	0.079
546	1368640	<5	<0.001	<0.005
547	1368641	191	0.006	0.191
548 Dup	1368641	186	0.005	0.186
549	1368642	13700	0.400	13.700
550	1368643	3131	0.091	3.131
551	1368644	341	0.010	0.341
552	1368645	313	0.009	0.313
553	1368646	213	0.006	0.213
554	1368647	7568	0.221	7.568
555	1368648	231	0.007	0.231
556	1368649	102	0.003	0.102
557	1368650	1936	0.056	1.936
558	1368651	1535	0.045	1.535
559 Dup	1368651	1750	0.051	1.750
560	1368652	819	0.024	0.819
561	1368653	252	0.007	0.252
562	1368654	30	<0.001	0.030
563	1368655	32	<0.001	0.032
564	1368656	11	<0.001	0.011
565	1368657	15	<0.001	0.015
566	1368658	114	0.003	0.114
567	1368659	30	<0.001	0.030

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Wednesday, January 23, 2013


Preliminary Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 01/04/2013
 Date Completed: 01/23/2013
 Job #: 201340005
 Reference: TL12-293
 Sample #: 41

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
568	1368660	6	<0.001	0.006
569	1368661	106	0.003	0.106
570 Dup	1368661	196	0.006	0.196
571	1368662	241	0.007	0.241
572	1368663	128	0.004	0.128
573	1368664	287	0.008	0.287
574	1368665	65	0.002	0.065
575	1368666	39	0.001	0.039
576	1368667	61	0.002	0.061
577	1368668	23	<0.001	0.023
578	1368669	16	<0.001	0.016
579	1368670	5039	0.147	5.039
580	1368671	19	<0.001	0.019
581 Dup	1368671	25	<0.001	0.025
582	1368672	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1

Certified By: 
 Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, January 21, 2013

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 01/04/2013
 Date Completed: 01/21/2013
 Job #: 201340006
 Reference: TL12-294
 Sample #: 92

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
583	1367892	29	<0.001	0.029
584	1367893	3339	0.097	3.339
585	1367894	107	0.003	0.107
586	1367895	140	0.004	0.140
587	1367896	102	0.003	0.102
588	1367897	40	0.001	0.040
589	1367898	25	<0.001	0.025
590	1367899	45	0.001	0.045
591	1367900	5300	0.155	5.300
592	1367901	34	<0.001	0.034
593 Dup	1367901	34	0.001	0.034
594	1367902	16	<0.001	0.016
595	1367903	19	<0.001	0.019
596	1367904	104	0.003	0.104
597	1367905	32	<0.001	0.032
598	1367906	32	<0.001	0.032
599	1367907	38	0.001	0.038
600	1367908	46	0.001	0.046
601	1367909	455	0.013	0.455
602	1367910	14	<0.001	0.014
603	1367911	85	0.002	0.085
604 Dup	1367911	75	0.002	0.075
605	1367912	44	0.001	0.044
606	1367913	30	<0.001	0.030
607	1367914	42	0.001	0.042
608	1367915	77	0.002	0.077
609	1367916	85	0.002	0.085
610	1367917	46	0.001	0.046
611	1367918	79	0.002	0.079
612	1367919	116	0.003	0.116

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, January 21, 2013

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 01/04/2013
 Date Completed: 01/21/2013
 Job #: 201340006
 Reference: TL12-294
 Sample #: 92

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
613	1367920	273	0.008	0.273
614	1367921	109	0.003	0.109
615 Dup	1367921	138	0.004	0.138
616	1367922	69	0.002	0.069
617	1367923	46	0.001	0.046
618	1367924	396	0.012	0.396
619	1367925	61	0.002	0.061
620	1367926	64	0.002	0.064
621	1367927	63	0.002	0.063
622	1367928	50	0.001	0.050
623	1367929	104	0.003	0.104
624	1367930	11	<0.001	0.011
625	1367931	92	0.003	0.092
626 Dup	1367931	169	0.005	0.169
627	1367932	183	0.005	0.183
628	1367933	210	0.006	0.210
629	1367934	259	0.008	0.259
630	1367935	161	0.005	0.161
631	1367936	183	0.005	0.183
632	1367937	223	0.007	0.223
633	1367938	554	0.016	0.554
634	1367939	117	0.003	0.117
635	1367940	1863	0.054	1.863
636	1367941	227	0.007	0.227
637 Dup	1367941	210	0.006	0.210
638	1367942	328	0.010	0.328
639	1367943	2725	0.080	2.725
640	1367944	2810	0.082	2.810
641	1367945	754	0.022	0.754
642	1367946	238	0.007	0.238

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, January 21, 2013

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 01/04/2013
 Date Completed: 01/21/2013
 Job #: 201340006
 Reference: TL12-294
 Sample #: 92

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
643	1367947	1738	0.051	1.738
644	1367948	253	0.007	0.253
645	1367949	181	0.005	0.181
646	1367950	15	<0.001	0.015
647	1367951	59	0.002	0.059
648 Rep	1367951	36	0.001	0.036
649	1367952	54	0.002	0.054
650	1367953	27	<0.001	0.027
651	1367954	108	0.003	0.108
652	1367955	91	0.003	0.091
653	1367956	51	0.001	0.051
654	1367957	77	0.002	0.077
655	1367958	924	0.027	0.924
656	1367959	108	0.003	0.108
657	1367960	5082	0.148	5.082
658	1367961	193	0.006	0.193
659 Dup	1367961	178	0.005	0.178
660	1367962	240	0.007	0.240
661	1367963	48	0.001	0.048
662	1367964	178	0.005	0.178
663	1367965	781	0.023	0.781
664	1367966	102	0.003	0.102
665	1367967	96	0.003	0.096
666	1367968	226	0.007	0.226
667	1367969	111	0.003	0.111
668	1367970	8	<0.001	0.008
669	1367971	71	0.002	0.071
670 Dup	1367971	61	0.002	0.061
671	1367972	48	0.001	0.048
672	1367973	73	0.002	0.073

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Monday, January 21, 2013


Preliminary Analysis

Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 01/04/2013
 Date Completed: 01/21/2013
 Job #: 201340006
 Reference: TL12-294
 Sample #: 92

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
673	1367974	67	0.002	0.067
674	1367975	152	0.004	0.152
675	1367976	94	0.003	0.094
676	1367977	104	0.003	0.104
677	1367978	266	0.008	0.266
678	1367979	48	0.001	0.048
679	1367980	256	0.007	0.256
680	1367981	19	<0.001	0.019
681 Dup	1367981	27	<0.001	0.027
682	1367982	70	0.002	0.070
683	1367983	17	<0.001	0.017

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, January 24, 2013

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 01/07/2013
 Date Completed: 01/24/2013
 Job #: 201340043
 Reference: TL12-295
 Sample #: 57

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
3438	1368673	27	<0.001	0.027
3439	1368674	279	0.008	0.279
3440	1368675	952	0.028	0.952
3441	1368676	40	0.001	0.040
3442	1368677	34	<0.001	0.034
3443	1368678	21	<0.001	0.021
3444	1368679	55	0.002	0.055
3445	1368680	6	<0.001	0.006
3446	1368681	89	0.003	0.089
3447	1368682	79	0.002	0.079
3448 Dup	1368682	66	0.002	0.066
3449	1368683	32	<0.001	0.032
3450	1368684	53	0.002	0.053
3451	1368685	39	0.001	0.039
3452	1368686	28	<0.001	0.028
3453	1368687	65	0.002	0.065
3454	1368688	116	0.003	0.116
3455	1368689	69	0.002	0.069
3456	1368690	234	0.007	0.234
3457	1368691	777	0.023	0.777
3458	1368692	207	0.006	0.207
3459 Dup	1368692	213	0.006	0.213
3460	1368693	916	0.027	0.916
3461	1368694	2616	0.076	2.616
3462	1368695	111	0.003	0.111
3463	1368696	83	0.002	0.083
3464	1368697	1026	0.030	1.026
3465	1368698	9969	0.291	9.969
3466	1368699	65	0.002	0.065
3467	1368700	<5	<0.001	<0.005

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, January 24, 2013

Preliminary Analysis

 Treasury Metals Inc
 Exchange Tower 130 King St Suite 3680
 Toronto, On, CAN
 M5X 1B1
 Ph#: (416) 599-4133
 Fax#: (416) 599-4959
 Email: rory@treasurymetals.com, dennis@treasurymetals.com

 Date Received: 01/07/2013
 Date Completed: 01/24/2013
 Job #: 201340043
 Reference: TL12-295
 Sample #: 57

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
3468	1368701	146	0.004	0.146
3469	1368702	206	0.006	0.206
3470 Dup	1368702	196	0.006	0.196
3471	1368703	13	<0.001	0.013
3472	1368704	10277	0.300	10.277
3473	1368705	271	0.008	0.271
3474	1368706	209	0.006	0.209
3475	1368707	2107	0.061	2.107
3476	1368708	219	0.006	0.219
3477	1368709	5734	0.167	5.734
3478	1368710	2081	0.061	2.081
3479	1368711	467	0.014	0.467
3480	1368712	2386	0.070	2.386
3481 Dup	1368712	2570	0.075	2.570
3482	1368713	235	0.007	0.235
3483	1368714	227	0.007	0.227
3484	1368715	42	0.001	0.042
3485	1368716	9	<0.001	0.009
3486	1368717	106	0.003	0.106
3487	1368718	337	0.010	0.337
3488	1368719	136	0.004	0.136
3489	1368720	<5	<0.001	<0.005
3490	1368721	95	0.003	0.095
3491	1368722	26	<0.001	0.026
3492 Dup	1368722	22	<0.001	0.022
3493	1368723	52	0.002	0.052
3494	1368724	283	0.008	0.283
3495	1368725	39	0.001	0.039
3496	1368726	62	0.002	0.062
3497	1368727	148	0.004	0.148

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


 Certified By: Dr. David Brown, VP Quality

 The results included on this report relate only to the items tested.
 The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.

Thursday, January 24, 2013


Preliminary Analysis

Treasury Metals Inc
Exchange Tower 130 King St Suite 3680
Toronto, On, CAN
M5X 1B1
Ph#: (416) 599-4133
Fax#: (416) 599-4959
Email: rory@treasurymetals.com, dennis@treasurymetals.com

Date Received: 01/07/2013
Date Completed: 01/24/2013
Job #: 201340043
Reference: TL12-295
Sample #: 57

Acc #	Client ID	Au ppb	Au oz/t	Au g/t (ppm)
3498	1368728	255	0.007	0.255
3499	1368729	30	<0.001	0.030

PROCEDURE CODES: ALP1, ALFA1, ALMA1, AISu1


Certified By: Dr. David Brown, VP Quality

The results included on this report relate only to the items tested.

The Certificate of Analysis should not be reproduced except in full, without the written approval of the laboratory.