

We are committed to providing [accessible customer service](#).
If you need accessible formats or communications supports, please [contact us](#).

Nous tenons à améliorer [l'accessibilité des services à la clientèle](#).
Si vous avez besoin de formats accessibles ou d'aide à la communication, veuillez [nous contacter](#).

ASSESSMENT REPORT

REPORT ON PROGRAM OF SAMPLING

ON THE

HISTORIC McDONALD PROPERTY

for Roy Annett

MACMURCHY TOWNSHIP, LARDER LAKE MINING DIVISION

June 2016
Joe-Anne Salo

Zone 17, 487382E, 5271902N

INTRODUCTION

Roy Annett, a prospector from ShiningTree, Ontario, acquired by staking during June 2002, a portion of the historic McDonald property in south-western Macmurchy Township, which came open as a result of Gazette non-payment of taxes. This short program was to collect samples for assays.

ACCESS

Access is by the old Violet Lake Road, which leaves highway 560 about five kilometres east of Shining Tree village. The Violet Lake Road is followed easterly for approximately two kilometres to a short branch road constructed by Annett et al, which leads onto claim 1046148, where stripping took place in 2002.

HISTORICAL COMMENTS

This claim is part of the McIntyre-McDonald claim group in the historic Wasapika section of the West Shining Tree gold area. A number of gold-bearing quartz veins were trenched and pitted on Claim TRS 2565 (now the Annett Property). A 55 foot shaft was sunk in the fall of 1912 at the side of Annetts north shaft stripping.

Gold was first discovered in the Shining Tree area in 1911 followed by a flurry of staking and prospecting which resulted in over a hundred recorded occurrences of native gold being found. Many of the occurrences were of a high-grade nature with some spectacular pockets being mined from shallow surface workings. These gold occurrences, however, never resulted in a mine but certainly created some fanciful and ill-advised developments where promoters would utilize the romance of some spectacular gold find to finance the building of a small mill and sink a shaft without the benefit of defining any ore reserves. Once the money ran out the project died. This land has been the history of the Shining Tree camp.

GENERAL GEOLOGY OF PROPERTY

Bedrock in the southwestern Macmurchy Township is predominantly steeply dipping Archean age dark green basalts, which trend in a northwest-southeast direction. Shear zones are a common occurrence in the area either paralleling the regional northwest-southeast trend of the country rocks or as fracture zones perpendicular to the trend. The shears are often rusty and carbonate rich and host quartz veins or quartz lenses. Pyrite is the most common sulphide in these shears. Gold is preferentially present in the quartz veining along with tourmaline and rarely galena.

CURRENT PROGRAM

The current program was to sample the area around the shaft. Larry Salo drove from Connaught and picked up Roy Annett and together they went to the property. There they did a little bit of mapping and sampling. Assays results are appended to this report.

RECOMMENDATIONS

This author recommends doing a survey encompassing the main vein that runs from the north shaft to the south shaft. Blasting could be used to determine if it is just on surface or if it has some depth to it, followed up by diamond drilling.

Respectfully submitted

A handwritten signature in cursive script that reads "Joe-Anne Salo".


Joe-Anne Salo
M21106
Client 191078

MAPS

General Location

Claim map

Abstract





MINISTRY OF NORTHERN DEVELOPMENT AND MINES
CLAIMaps


MACMURCHY

Notes:
Enter map notes



Legend

- Administration Boundaries**
 - Mining Divisions
 - Resident Geological District
 - Townships and Aces
- Mineral Tenure Grid**
 - OMTG Tenure Grid
- Alienations**
 - Withdrawal
 - Notice
- Unpatented Claim**
 - Active
 - Pending
- Disposition**
 - Disposition
- Disposition Symbols**
 - Camp
 - Disposition Unknown/Pending
 - Freehold Patent Mining Rights Only
 - Freehold Patent Surface Rights Only
 - Freehold Patent Surface and Mining Rights
 - Freehold Patent Surface and Mining
 - Land Use Permit
 - Leasehold Patent Mining Rights Only
 - Leasehold Patent Surface Rights Only
 - Leasehold Patent Surface and Mining Rights
 - License of Occupation Mining Use Only
 - License of Occupation Mining Use Only
 - License of Occupation Surface and Mining Rights
 - License of Occupation Surface and Mining
 - License of Occupation Uses Not Specified
 - Open in Court
 - Other
 - Tr. W.P.A.
- Geology Layers**
 - AMIS Sites
 - AMIS Features
 - Dirt Holes
 - Mineral Occurrences



Projection: Web Mercator



The Ontario Ministry of Northern Development and Mines shall not be liable in any way for the use of, or reliance upon, this map or any information on this map. This map should not be used for navigation, a plan of survey, routes, nor locations.
© Queen's Printer for Ontario, 2016

Imagery Copyright Notices: Ontario Ministry of Natural Resources and Forestry, NASA Landsat Program; First Base Solutions Inc.; Aéro-Photo (1961) Inc.; DigitalGlobe Inc.; U.S. Geological Survey.
© Copyright for Ontario Parcel data is held by Queen's Printer for Ontario and its licensors and may not be reproduced without permission.

Mining Claim Abstract
[| Main Menu](#) | [Back](#) |

LARDER LAKE - Division 80		Claim Number: L 1046148	Status: ACTIVE
Due Date:	2016-Jun-04	Recorded:	2002-Jun-04
Work Required:	\$800	Staked:	2002-Jun-01 10:42
Total Work:	\$9,600	Township/Area:	MACMURCHY (G-0988)
Total Reserve:	\$280	Lot Description:	
Present Work Assignment:	\$0	Claim Units:	2
Claim Bank:	\$0		

Claim Holders
Recorded Holder(s) Percentage
 ANNETT, ROY (100.00 %)

Client Number
 102630


Transaction Listing

Type	Date	Applied	Description	Performed	Number
STAKER	2002-Jun-04		SALO, LARRY JOHN (191085) RECORDS 100.00 % IN THE NAME OF ANNETT, ROY (102630)		R0280.02263
STAKER	2002-Jun-04		RECORDED BY SALO, LARRY JOHN (M20010)		R0280.01995
OTHER	2003-Apr-11		WORK PERFORMED (ASSAY, GEOL, LC, PSTRIIP) APPROVED: 2003-MAY-12	\$17,080	Q0380.00618
WORK	2003-Apr-11	\$4,000	WORK APPLIED (ASSAY, GEOL, LC, PSTRIIP) APPROVED: 2003-MAY-12		W0380.00618
WORK	2009-May-25	\$3,200	WORK APPLIED		W0980.01420
WORK	2013-Feb-14	\$1,600	WORK APPLIED		W1380.00868
OTHER	2015-Jun-01		WORK PERFORMEDGPSG APPROVED: 2015-JUN-03	\$800	Q1580.01210
WORK	2015-Jun-01	\$800	WORK APPLIEDGPSG APPROVED: 2015-JUN-03		W1580.01210

Claim Reservations

- 01 400' surface rights reservation around all lakes and rivers
- 02 Sand and gravel reserved
- 03 Peat reserved
- 04 Other reservations under the Mining Act may apply
- 05 Including land under water

TRAVERSES
PHOTOS OF SAMPLES



MUCK

Rusty Carb-rich

North Shaft

diabase dyke

5271550N

Main qtz vein
18"

edge of
old
stripping

Capped
South Shaft

5271600N

#3 post

5271485N

486850

486900

486950

0 10 20 30m

→ traverse

0 1 2 3cm

1cm = 10m



Sample 1- assay ticket 1404956- 74.2g/t Au
486934E, 5271561N



Sample 2- Assay Ticket 14049577- 80.4g/t Au
486936E, 5271563N



Close up of visible gold in sample 2- assay ticket 1404957

ASSAY RESULTS

Quality Analysis ...



Innovative Technologies

This is your final copy. If you require an original to be mailed by post please advise, otherwise this email will be deemed sufficient.

Invoice No.: A16-04635
Purchase Order:
Invoice Date: 01-Jun-16
Date submitted: 24-May-16
Your Reference: Benoit
GST #: R121979355

AIX
Timmins ON
Canada

ATTN: JG Salo

INVOICE

Table with 4 columns: No. samples, Description, Unit Price, Total. Includes handwritten calculations on the left and a signature 'Benoit' at the bottom.

Handwritten signature: Marchurthy

Net 30 days. 1 1/2 % per month charged on overdue accounts.
THE ABOVE AMOUNT HAS BEEN CHARGED TO VISA. THANK YOU!
AUTH#000776-JUNE 3/16

Please reference the invoice number when making a payment by Bank/Wire transfer. Intermediary Bank Fees are the responsibility of the client. If payment is made by direct/wire transfer, please send payment notifications to ancaster@actlabs.com Thank you!

ACTIVATION LABORATORIES LTD.
41 Bittern Street, Ancaster, Ontario Canada L9G 4V5 TELEPHONE +1.905.648.9611 or +1.888.228.5227 FAX +1.905.648.9613
E-MAIL ancaster@actlabs.com ACTLABS GROUP WEBSITE http://www.actlabs.com



Quality Analysis ...



Innovative Technologies

Date Submitted: 24-May-16
Invoice No.: A16-04635
Invoice Date: 03-Jun-16
Your Reference: Benoit

AIX

Timmins ON
Canada

ATTN: JG Salo

CERTIFICATE OF ANALYSIS

9 Rock samples were submitted for analysis.

The following analytical package(s) were requested:

Code 1A2-Timmins Au - Fire Assay AA

Code 1E2-Timmins Aqua Regia ICP(AQUAGEO)

REPORT A16-04635

This report may be reproduced without our consent. If only selected portions of the report are reproduced, permission must be obtained. If no instructions were given at time of sample submittal regarding excess material, it will be discarded within 90 days of this report. Our liability is limited solely to the analytical cost of these analyses. Test results are representative only of material submitted for analysis.

Notes:

If value exceeds upper limit we recommend reassay by fire assay gravimetric-Code 1A3.

Values which exceed the upper limit should be assayed for accurate numbers.

CERTIFIED BY:

A handwritten signature in black ink, appearing to be "Emmanuel Eseme". The signature is written in a cursive, somewhat stylized font.

Emmanuel Eseme, Ph.D.
Quality Control

ACTIVATION LABORATORIES LTD.
1752 Riverside Drive, Timmins, Ontario, Canada, P4R 1N1
TELEPHONE +705 264-0123 or +1.888.228.5227 FAX +1.905.648.9613
E-MAIL Timmins@actlabs.com ACTLABS GROUP WEBSITE www.actlabs.com

Results

Analyte Symbol	Au	Ag	Cd	Cu	Mn	Mo	Ni	Pb	Zn	Al	As	B	Ba	Be	Bi	Ca	Co	Cr	Fe	Ga	La	K	Mg
Unit Symbol	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	%
Lower Limit	5	0.2	0.2	1	1	2	1	2	1	0.01	3	5	1	1	2	0.01	1	2	0.01	1	1	1	0.01
Method Code	FA-AA	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP
1404856	> 5000																						
1404857	> 5000																						
1404858	2740																						
1404859	3120																						
1404860	483																						
1404861	1420																						
1404862	216																						
1404863	953																						
1404864	6	< 0.2	< 0.2	1240	321	< 2	52	< 2	28	1.72	< 3	< 5	23	< 1	< 2	1.01	14	150	3.37	13	20	< 0.01	1.51

Cinnatti
Stavros

Analyte Symbol	Na	P	Sb	Sc	Se	Sn	Sr	Te	Tl	Ti	U	V	W	Y	Zr	S	Au
Unit Symbol	%	%	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	%	g/tonne
Lower Limit	0.001	0.001	5	0.1	5	5	1	1	2	0.01	10	1	1	1	1	0.001	0.03
Method Code	AR-ICP	AR-ICP	AR-JCP	AR-JCP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	FA-GRA
1404955																	74.2
1404957																	80.4
1404958																	
1404959																	
1404960																	
1404961																	
1404962																	
1404963																	
1404964	0.138	0.059	< 5	7.2	< 5	< 5	< 5	5	< 1	< 2	< 0.01	< 10	98	< 1	11	16	0.016

Handwritten signature

Analyte Symbol	Au	Ag	Cd	Cu	Mn	Mo	Ni	Pb	Zn	Al	As	B	Ba	Be	Bi	Ca	Co	Cr	Fe	Ga	La	K	Mg
Unit Symbol	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	%
Lower Limit	5	0.2	0.2	1	1	2	1	2	1	0.01	3	5	1	1	2	0.01	1	2	0.01	1	1	0.01	0.01
Method Code	FA-AA	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP
GXR-1 Meas		28.7	2.4	1110	748	13	30	585	685	0.35	365	9	471	<1	<1	1510	0.78	6	22.8	5	5	0.03	0.13
GXR-1 Cert		31.0	3.30	1110	652	18.0	41.0	730	760	3.52	427	15.0	750	1.22	1380	0.960	8.20	12.0	23.6	13.8	7.50	0.050	0.217
GXR-4 Meas		3.8	0.4	6310	132	305	33	42	72	2.87	96	<5	58	1	18	0.89	13	56	3.15	10	48	1.63	1.61
GXR-4 Cert		4.0	0.660	6520	165	310	42.0	52.0	73.0	7.20	98.0	4.50	1640	1.90	18.0	1.01	14.6	64.0	3.08	20.0	64.5	4.01	1.66
GXR-5 Meas		0.5	<0.2	66	690	<2	21	87	123	7.34	244	<5	1060	<1	<2	0.16	13	77	5.62	16	11	1.07	0.39
GXR-5 Cert		1.30	1.00	66.0	1010	2.40	27.0	101	118	17.7	330	9.80	1300	1.40	0.290	0.180	13.8	96.0	5.58	35.0	13.9	1.87	0.609
OXD108 Meas	409																						
OXD108 Cert	414																						
OXN117 Meas																							
OXN117 Cert																							
OPP91 Meas																							
OPP91 Cert																							
OXJ120 Meas	2260																						
OXJ120 Cert	2355.000																						
1404664 Orig		<0.2	<0.2	1250	323	<2	53	3	28	1.72	<3	<5	23	<1	<2	1.02	14	149	3.39	13	19	0.01	1.62
1404664 Dup		<0.2	<0.2	1240	319	<2	52	<2	26	1.72	<3	<5	23	<1	<2	1.01	14	150	3.35	13	20	<0.01	1.61
Method Blank		<0.2	<0.2	<1	<1	<2	<1	<2	<1	<0.01	<3	<5	13	<1	<2	<0.01	<1	<2	<0.01	<1	<1	<0.01	<0.01
Method Blank	<5																						
Method Blank	<5																						
Method Blank																							
Method Blank																							

Analyte Symbol	Na	P	Sb	Sc	Se	Sn	Sr	Te	Ti	Tl	U	V	W	Y	Zr	S	Au
Unit Symbol	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	%	g/tone
Lower Limit	0.001	0.001	5	0.1	5	5	1	1	2	0.01	10	1	1	1	1	0.001	0.03
Method Code	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	AR-ICP	FA-GRA
GXR-1 Meas	0.054	0.036	87	1.0	6	24	188	9	<2	<0.01	28	81	153	24	15	0.187	
GXR-1 Cert	0.0520	0.0650	122	1.58	16.6	54.0	275	13.0	0.390	0.036	34.9	80.0	164	32.0	38.0	0.257	
GXR-4 Meas	0.139	0.115	6	6.3	<5	7	69	2	2	0.13	<10	84	15	12	10	1.68	
GXR-4 Cert	0.0584	0.120	4.90	7.70	5.60	5.60	221	0.970	3.20	0.29	6.20	87.0	30.8	14.0	186	1.77	
GXR-6 Meas	0.082	0.031	<5	21.8	<5	<5	31	<2	<2		<10	184	<1	6	15	0.014	
GXR-6 Cert	0.104	0.0350	3.60	27.6	0.940	1.70	35.0	0.0180	2.20		1.54	186	1.90	14.0	110	0.0160	
OxD108 Meas																	
OxD108 Cert																	7.87
OXN117 Meas																	7.678
OXN117 Cert																	14.9
OxP91 Meas																	14.82
OxP91 Cert																	
OxJ120 Meas																	
OxJ120 Cert																	
HO4954 Orig	0.137	0.059	<5	7.2	<5	<5	5	<1	<2	<0.01	<10	98	<1	11	16	0.017	
HO4954 Dup	0.138	0.058	<5	7.2	<5	<5	6	<1	<2	<0.01	<10	97	<1	11	16	0.016	
Method Blank	0.015	<0.001	<5	<0.1	<5	<5	<1	<1	<2	<0.01	<10	<1	<1	<1	<1	<0.001	
Method Blank																	
Method Blank																	
Method Blank																	<0.03
Method Blank																	<0.03