ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 20-JUN-2018
Account: BMRPLLBW

CERTIFICATE SD18133994

Project: IRON MASK

This report is for 104 Drill Core samples submitted to our lab in Sudbury, ON, Canada on 7-JUN-2018.

The following have access to data associated with this certificate:

SANDY DE LA MARE	PETER DOYLE	JON EDWARDS
MIKE HENDRICKSON	FRANK PLOEGER	IAN PRINGLE
MERCEDES RICH	CLYDE SMITH	

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
LOG-24	Pulp Login - Rcd w/o Barcode
CRU-31	Fine crushing - 70% <2mm
CRU-QC	Crushing QC Test
PUL-QC	Pulverizing QC Test
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
ME-OG62	Ore Grade Elements - Four Acid	ICP-AES
Cu-OG62	Ore Grade Cu - Four Acid	ICP-AES
Ni-OG62	Ore Grade Ni - Four Acid	ICP-AES
ME-MS61	48 element four acid ICP-MS	
Ag-OG62	Ore Grade Ag - Four Acid	ICP-AES

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

***** See Appendix Page for comments regarding this certificate *****

Signature:
Colin Ramshaw, Vancouver Laboratory Manager

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 20-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18133994

Sample Description	Method / Analyte / Units / LOD	WEI-21 Recvd Wt. kg 0.02	ME-MS61 Ag ppm 0.01	ME-MS61 Al % 0.01	ME-MS61 As ppm 0.2	ME-MS61 Ba ppm 10	ME-MS61 Be ppm 0.05	ME-MS61 Bi ppm 0.01	ME-MS61 Ca % 0.01	ME-MS61 Cd ppm 0.02	ME-MS61 Ce ppm 0.01	ME-MS61 Co ppm 0.1	ME-MS61 Cr ppm 1	ME-MS61 Cs ppm 0.05	ME-MS61 Cu ppm 0.2	ME-MS61 Fe % 0.01
9315		2.32	<0.01	7.91	0.7	640	1.04	<0.01	5.20	0.11	53.3	51.3	55	1.06	31.4	10.25
9316		1.85	0.02	7.63	2.5	570	1.52	<0.01	4.91	0.47	55.2	47.9	51	1.15	39.2	10.05
9317		1.95	<0.01	7.14	1.9	90	1.38	0.02	0.32	0.03	47.2	20.4	111	0.44	2.4	4.19
9318		1.46	<0.01	6.75	1.9	90	1.70	0.06	0.29	<0.02	50.4	27.5	108	0.59	8.1	4.11
9319		1.06	<0.01	6.10	0.8	30	1.09	0.01	0.25	<0.02	21.4	11.3	100	0.07	2.3	3.64
9320		0.87	<0.01	7.12	1.8	50	1.39	0.03	0.27	<0.02	40.9	24.4	113	0.09	1.4	3.63
9321		0.07	4.03	5.47	13.8	120	0.55	0.80	3.44	2.13	17.30	962	272	0.78	>10000	17.75
9322		1.97	0.02	7.18	2.3	140	2.34	0.11	0.33	0.03	46.0	45.2	108	0.16	7.0	3.84
9323		2.30	0.02	6.84	1.9	60	1.81	0.10	0.31	<0.02	111.0	45.1	106	0.12	3.7	5.30
9324		1.85	0.02	6.90	2.6	70	1.85	0.11	0.26	<0.02	32.7	58.5	114	0.11	2.5	4.05
9325		1.01	0.01	0.08	<0.2	20	<0.05	<0.01	33.5	0.02	1.10	2.0	4	<0.05	3.6	0.13
9326		2.03	0.01	6.64	1.0	70	1.35	0.05	0.26	<0.02	31.9	43.5	106	0.12	2.3	4.08
9327		2.19	0.01	6.70	2.0	50	1.20	0.05	0.25	<0.02	22.2	30.3	102	0.09	2.7	5.90
9328		2.15	0.01	6.62	3.3	70	1.01	0.06	0.31	<0.02	58.7	25.4	110	0.11	2.6	4.15
9329		2.02	0.01	7.03	4.0	70	1.07	0.13	0.41	<0.02	29.7	81.2	108	0.11	4.1	4.27
9330		1.69	0.04	8.52	8.4	20	0.78	1.30	0.49	<0.02	7.71	476	133	<0.05	4.1	2.60
9331		2.04	0.06	9.16	8.8	20	0.90	1.54	0.48	<0.02	26.2	424	128	<0.05	3.2	2.37
9332		2.02	0.05	9.25	12.7	20	0.99	1.32	0.54	<0.02	16.45	435	117	<0.05	6.6	2.35
9333		2.03	0.13	8.87	14.9	20	1.11	1.66	0.43	<0.02	5.55	435	121	<0.05	6.3	2.47
9334		2.06	0.14	8.23	5.4	20	1.04	0.90	0.52	<0.02	6.94	160.0	101	<0.05	3.5	1.67
9335		2.06	0.07	8.53	6.5	20	1.09	0.54	0.47	<0.02	7.55	142.5	130	<0.05	2.2	1.89
9336		2.15	0.04	7.97	6.7	40	1.07	0.35	0.41	<0.02	12.90	139.5	138	0.06	2.1	2.72
9337		1.28	0.01	7.47	7.7	30	0.94	0.56	0.32	<0.02	7.29	303	159	<0.05	2.9	2.85
9338		2.21	0.01	7.32	3.6	130	1.45	0.10	0.34	<0.02	25.1	76.7	134	0.20	2.6	5.21
9339		2.25	<0.01	7.16	3.1	130	1.07	0.04	1.29	<0.02	39.5	19.2	111	0.28	9.0	5.40
9340		2.26	0.01	6.90	7.1	100	1.16	0.08	0.41	<0.02	39.0	27.3	129	0.21	2.2	4.77
9341		2.26	0.01	7.11	3.4	120	1.22	0.05	1.00	<0.02	34.9	18.4	111	0.28	6.5	4.21
9342		2.24	0.02	7.22	3.0	440	1.22	0.26	1.74	<0.02	42.6	25.0	107	1.30	72.6	4.70
9343		2.57	0.01	7.30	5.0	380	1.00	0.08	1.09	<0.02	29.8	22.4	99	1.61	2.4	4.81
9344		2.33	0.03	7.21	2.2	270	1.02	0.04	0.66	0.03	37.6	17.1	98	1.12	6.6	3.79
9345		2.50	0.09	6.75	6.4	530	0.94	0.13	0.48	0.28	32.8	14.7	80	2.92	115.5	4.32
9346		1.90	0.18	6.08	13.8	450	1.12	0.28	1.16	0.08	57.0	10.7	74	2.67	446	5.06
9351		2.15	0.09	6.62	42.5	860	1.54	2.02	2.06	0.04	108.0	38.9	88	5.37	28.8	5.41
9352		2.03	0.17	5.91	41.8	1700	0.97	4.90	2.76	0.04	21.3	28.5	57	4.27	80.6	4.28
9353		1.81	0.24	5.81	70.6	2070	1.68	13.35	4.32	0.05	26.2	41.6	67	2.01	113.0	4.56
9354		2.02	0.12	5.84	56.6	2580	2.93	11.95	4.23	0.03	73.6	37.5	54	2.90	28.8	5.51
9355		2.24	0.04	6.10	42.4	2250	1.82	4.25	5.92	0.02	61.8	29.2	65	0.68	13.4	4.00
9356		1.82	0.04	6.47	14.9	1390	2.11	0.44	0.55	0.12	69.4	13.8	85	1.61	54.2	2.64
9357		1.91	0.07	5.70	15.9	2350	1.64	2.37	3.32	0.16	62.4	14.2	31	1.20	44.1	3.03
9358		2.09	0.03	5.94	2.8	1700	2.08	0.29	2.49	<0.02	68.4	6.5	66	1.88	14.7	2.61

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 20-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18133994

Sample Description	Method / Analyte / Units / LOD	ME-MS61 Ga ppm 0.05	ME-MS61 Ge ppm 0.05	ME-MS61 Hf ppm 0.1	ME-MS61 In ppm 0.005	ME-MS61 K % 0.01	ME-MS61 La ppm 0.5	ME-MS61 Li ppm 0.2	ME-MS61 Mg % 0.01	ME-MS61 Mn ppm 5	ME-MS61 Mo ppm 0.05	ME-MS61 Na % 0.01	ME-MS61 Nb ppm 0.1	ME-MS61 Ni ppm 0.2	ME-MS61 P ppm 10	ME-MS61 Pb ppm 0.5
9315		21.3	0.19	4.8	0.085	1.19	22.8	23.7	3.75	1380	1.13	2.15	13.1	78.4	3580	4.1
9316		19.80	0.17	4.2	0.086	1.01	23.9	43.5	4.52	1120	1.53	1.75	12.1	71.9	3260	120.5
9317		16.80	0.13	3.0	0.019	0.31	22.0	30.6	1.80	208	1.34	4.31	4.3	44.9	520	5.1
9318		16.15	0.15	2.8	0.019	0.42	23.1	32.1	1.72	191	1.33	3.89	4.1	46.2	480	6.7
9319		13.85	0.12	2.4	0.011	0.11	10.3	6.0	0.84	110	3.45	4.21	2.7	25.0	400	2.0
9320		16.10	0.13	3.1	0.015	0.16	18.5	9.7	1.49	161	2.13	4.61	4.0	41.4	450	1.7
9321		11.75	0.50	1.3	0.113	0.31	7.3	8.9	4.02	1000	4.45	1.17	5.0	>10000	460	14.6
9322		19.25	0.13	2.7	0.023	0.35	23.1	14.6	1.67	188	4.00	4.20	6.7	51.9	480	2.1
9323		17.95	0.16	2.6	0.020	0.19	56.8	12.1	1.39	162	3.31	4.21	4.2	41.7	410	2.1
9324		16.80	0.11	2.7	0.017	0.19	15.6	14.5	1.71	191	1.76	4.09	4.0	51.3	420	1.6
9325		0.30	0.05	0.1	<0.005	0.01	1.2	1.2	1.80	121	0.26	0.04	0.1	1.4	80	0.8
9326		14.35	0.07	2.4	0.018	0.20	14.3	8.5	1.45	165	2.14	4.08	3.3	40.7	390	1.6
9327		15.50	0.07	2.4	0.013	0.14	9.8	7.3	1.28	145	1.93	4.23	2.6	35.7	390	1.9
9328		15.20	0.11	2.2	0.019	0.19	30.3	7.3	1.28	162	6.13	4.19	2.8	35.0	400	1.9
9329		18.30	0.08	2.5	0.016	0.20	14.0	11.8	1.86	193	3.84	3.99	4.0	48.2	420	1.8
9330		20.9	0.09	3.1	<0.005	0.09	2.9	2.7	0.36	62	72.5	6.88	5.4	25.7	480	3.5
9331		24.3	0.11	3.0	0.005	0.10	12.5	3.1	0.41	66	94.4	7.49	4.7	26.7	540	5.2
9332		23.0	0.10	2.8	<0.005	0.10	7.2	2.5	0.31	56	52.8	7.65	5.5	26.4	700	4.7
9333		23.3	0.09	2.8	0.005	0.11	2.0	3.4	0.43	69	50.7	7.20	5.3	29.0	560	6.8
9334		22.0	0.11	2.5	0.006	0.11	2.7	2.8	0.38	63	131.5	7.02	3.9	18.0	550	5.8
9335		23.5	0.11	2.6	0.005	0.10	2.8	3.0	0.43	75	78.0	7.10	4.4	18.5	580	3.3
9336		20.6	0.10	2.5	0.008	0.14	6.0	4.8	0.73	112	18.85	6.03	3.8	27.1	480	2.4
9337		19.05	0.11	2.5	0.006	0.10	3.4	3.7	0.55	108	13.55	5.80	3.5	27.2	490	2.5
9338		18.90	0.12	2.4	0.025	0.37	11.0	13.1	2.21	238	1.76	3.86	3.8	61.9	480	1.7
9339		17.60	0.12	2.2	0.041	0.38	19.1	15.0	2.88	377	1.36	3.43	3.7	60.2	450	1.9
9340		16.60	0.11	2.3	0.021	0.31	18.5	13.6	2.61	270	0.94	3.56	3.9	55.0	440	1.7
9341		16.05	0.10	2.3	0.026	0.34	16.5	15.0	2.64	306	1.17	3.51	3.8	54.3	440	1.8
9342		18.10	0.12	2.3	0.058	1.04	19.7	17.2	3.20	711	2.01	2.84	4.6	66.1	540	4.2
9343		18.25	0.11	2.4	0.027	1.09	13.1	16.0	3.42	726	1.17	3.23	4.4	60.8	490	4.3
9344		17.05	0.13	2.9	0.007	0.70	18.7	13.3	2.49	589	1.74	4.00	5.2	51.3	450	9.6
9345		15.30	0.11	2.4	0.010	1.50	16.9	13.5	2.02	496	1.34	3.48	4.3	46.0	420	25.0
9346		14.75	0.12	2.2	0.044	1.30	36.1	12.4	1.81	621	0.99	3.33	4.1	52.9	440	8.4
9351		18.80	0.16	2.8	0.074	2.41	50.5	12.3	1.56	871	1.69	3.44	4.8	28.6	490	10.3
9352		13.05	0.12	2.7	0.075	3.92	9.7	8.8	0.76	721	1.29	1.74	4.2	23.1	460	12.1
9353		12.15	0.12	3.2	0.181	3.87	11.7	6.1	0.89	890	1.52	1.42	4.9	23.8	690	15.4
9354		14.90	0.17	2.9	0.195	3.82	37.1	8.4	0.97	875	0.97	1.38	6.2	20.1	560	13.5
9355		13.60	0.14	3.8	0.113	4.00	31.1	3.4	0.71	974	1.51	1.05	6.2	18.9	570	8.7
9356		16.15	0.12	4.4	0.019	3.75	36.3	9.4	0.73	188	1.91	2.40	7.1	25.1	490	18.0
9357		13.75	0.14	2.9	0.064	4.10	34.6	13.0	0.62	329	0.82	1.02	7.0	17.2	250	25.7
9358		14.95	0.14	4.3	0.071	3.92	37.2	8.9	0.69	332	1.81	1.65	7.6	17.9	430	13.0

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 20-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18133994

Sample Description	Method / Analyte / Units / LOD	ME-MS61 Rb ppm 0.1	ME-MS61 Re ppm 0.002	ME-MS61 S % 0.01	ME-MS61 Sb ppm 0.05	ME-MS61 Sc ppm 0.1	ME-MS61 Se ppm 1	ME-MS61 Sn ppm 0.2	ME-MS61 Sr ppm 0.2	ME-MS61 Ta ppm 0.05	ME-MS61 Te ppm 0.05	ME-MS61 Th ppm 0.01	ME-MS61 Ti % 0.005	ME-MS61 Tl ppm 0.02	ME-MS61 U ppm 0.1	ME-MS61 V ppm 1
9315		31.0	<0.002	0.09	0.05	22.0	<1	1.4	538	0.80	<0.05	1.21	1.730	0.31	0.3	211
9316		44.0	<0.002	0.09	0.28	20.7	1	1.3	452	0.72	<0.05	1.29	1.575	0.27	0.4	195
9317		7.9	0.003	0.12	0.13	11.3	1	0.9	106.5	0.39	<0.05	5.45	0.279	0.07	1.9	84
9318		12.5	<0.002	0.20	0.19	11.1	1	0.9	84.1	0.38	<0.05	5.26	0.264	0.10	1.9	79
9319		3.7	0.003	0.07	0.09	7.9	1	0.9	65.0	0.27	<0.05	4.38	0.186	0.02	2.2	84
9320		5.8	<0.002	0.15	0.08	10.2	1	0.9	86.7	0.37	<0.05	5.43	0.255	0.03	2.1	74
9321		10.5	0.045	8.55	3.25	8.4	21	2.6	183.0	0.32	4.69	1.07	0.533	0.17	0.4	78
9322		14.7	0.002	0.23	0.15	14.3	1	1.4	113.5	0.44	<0.05	5.04	0.265	0.06	2.1	75
9323		7.6	<0.002	0.23	0.14	15.0	1	1.4	93.3	0.35	<0.05	4.55	0.226	0.04	2.3	85
9324		7.8	<0.002	0.28	0.12	13.2	1	1.0	95.9	0.34	<0.05	4.27	0.243	0.03	1.7	74
9325		0.4	<0.002	0.01	0.09	0.3	1	<0.2	82.0	<0.05	<0.05	0.07	0.008	<0.02	0.2	1
9326		7.1	<0.002	0.24	0.12	9.8	<1	1.1	85.5	0.32	<0.05	3.75	0.230	0.03	1.6	80
9327		4.7	<0.002	0.20	0.11	10.6	1	1.1	74.0	0.29	<0.05	3.92	0.204	0.02	1.6	99
9328		7.0	<0.002	0.16	0.17	10.9	<1	0.6	89.0	0.27	<0.05	3.26	0.246	0.03	1.4	107
9329		7.3	<0.002	0.35	0.14	10.7	1	0.8	95.4	0.35	<0.05	3.63	0.279	0.03	2.1	92
9330		1.5	0.006	1.76	0.18	5.2	3	1.3	49.6	0.41	0.23	3.55	0.374	0.02	9.3	43
9331		1.7	0.008	1.50	0.17	6.6	3	0.9	51.0	0.38	0.28	4.20	0.327	0.03	17.4	40
9332		1.7	0.005	1.60	0.19	6.0	3	1.2	57.4	0.40	0.24	3.21	0.377	0.02	17.0	39
9333		2.1	0.005	1.66	0.24	5.8	3	1.3	55.2	0.37	0.24	3.40	0.363	0.03	35.9	36
9334		2.1	0.015	0.72	0.22	4.9	2	0.8	56.1	0.30	0.22	3.70	0.303	0.04	29.9	30
9335		2.0	0.011	0.62	0.18	6.9	2	0.9	54.6	0.37	0.14	3.46	0.373	0.02	10.9	36
9336		4.0	0.003	0.73	0.17	7.5	2	1.1	58.1	0.30	0.08	2.41	0.350	0.02	4.0	50
9337		2.6	<0.002	1.32	0.20	5.0	2	1.0	57.4	0.27	0.09	2.87	0.335	<0.02	3.0	43
9338		14.8	<0.002	0.38	0.14	14.9	1	2.1	94.8	0.32	<0.05	3.03	0.322	0.06	1.2	106
9339		14.0	<0.002	0.07	0.18	18.3	1	0.9	152.0	0.29	<0.05	3.34	0.341	0.08	0.8	132
9340		12.4	<0.002	0.23	0.13	14.3	<1	0.8	79.3	0.32	<0.05	2.90	0.314	0.06	1.1	107
9341		13.9	<0.002	0.10	0.15	16.0	1	0.7	111.0	0.33	<0.05	2.74	0.317	0.08	1.0	113
9342		48.8	<0.002	0.17	0.23	18.7	1	1.0	254	0.40	<0.05	3.21	0.412	0.38	1.2	140
9343		53.8	<0.002	0.07	0.21	18.4	1	0.8	184.0	0.36	<0.05	3.50	0.392	0.45	1.0	135
9344		47.4	<0.002	0.03	0.18	14.6	1	0.5	113.5	0.47	<0.05	5.22	0.316	0.31	1.6	109
9345		118.5	<0.002	0.34	0.14	12.2	<1	0.4	105.0	0.41	<0.05	4.18	0.273	0.70	1.3	89
9346		103.5	0.002	0.72	0.19	10.6	2	0.6	76.7	0.40	<0.05	4.71	0.224	0.63	1.6	71
9351		192.5	0.002	0.05	0.22	15.3	1	0.8	128.0	0.44	<0.05	4.96	0.282	0.95	2.2	86
9352		174.0	<0.002	0.11	0.18	6.0	1	0.7	60.4	0.41	0.08	6.34	0.143	0.89	2.4	37
9353		113.5	<0.002	0.12	0.27	6.6	1	1.2	67.1	0.51	0.05	6.39	0.171	0.59	2.8	41
9354		164.5	<0.002	0.08	0.22	5.5	1	1.2	125.5	0.56	0.14	10.20	0.154	0.78	3.2	30
9355		84.3	<0.002	0.02	0.28	7.1	1	3.1	136.0	0.58	0.05	8.63	0.183	0.40	3.2	35
9356		160.5	<0.002	0.07	0.12	7.6	<1	0.8	54.1	0.69	<0.05	10.30	0.220	0.78	4.9	48
9357		154.0	<0.002	0.08	0.18	3.5	1	1.4	77.8	0.55	<0.05	19.05	0.121	0.80	4.0	18
9358		182.5	0.002	0.05	0.21	6.2	<1	2.1	142.5	0.71	<0.05	15.20	0.191	0.96	4.9	37

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 20-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18133994

Sample Description	Method / Analyte / Units / LOD	ME-MS61 W ppm 0.1	ME-MS61 Y ppm 0.1	ME-MS61 Zn ppm 2	ME-MS61 Zr ppm 0.5	Ag-OG62 Ag ppm 1	Cu-OG62 Cu % 0.001	Ni-OG62 Ni % 0.001	CRU-QC Pass2mm % 0.01	PUL-QC Pass75um % 0.01
9315		0.2	31.2	127	183.5				83.4	86.1
9316		0.3	33.2	225	170.5					88.0
9317		0.4	11.7	14	104.0					
9318		0.4	11.2	14	98.7					
9319		0.5	9.5	7	84.0					
9320		0.5	11.7	11	107.0					
9321		2.2	9.2	138	51.5		1.620	4.69		
9322		0.6	10.3	24	99.7					
9323		1.0	12.5	15	98.8					
9324		0.6	9.9	15	101.0					
9325		<0.1	2.1	4	2.0					
9326		1.3	8.0	12	88.6					
9327		0.7	8.9	11	84.6					
9328		1.1	6.9	11	80.2					
9329		0.5	7.5	16	92.1					
9330		0.6	9.1	3	112.5					
9331		0.3	10.7	4	111.5					
9332		0.4	12.2	4	101.0					
9333		0.6	12.5	4	103.0					
9334		0.7	10.5	3	93.3					
9335		0.7	10.8	4	93.1					
9336		0.8	8.3	6	92.6					
9337		1.1	6.2	5	91.7					
9338		0.6	9.4	17	91.2					
9339		0.5	13.2	22	78.5					
9340		0.4	13.0	19	84.0					
9341		0.5	13.2	24	84.3					
9342		0.6	15.3	77	85.0					
9343		0.4	13.0	62	87.6					
9344		0.4	13.6	123	102.5					
9345		0.3	11.7	167	84.2					
9346		0.2	10.2	78	77.3					
9351		0.3	14.5	61	100.0					
9352		0.2	9.5	41	96.8					
9353		0.3	12.4	38	118.0					
9354		0.3	14.6	46	103.0					
9355		0.4	16.0	39	134.5					
9356		0.5	13.8	38	164.0					
9357		0.3	13.0	44	101.5					
9358		0.7	16.0	20	150.0				82.1	99.3

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 20-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18133994

Sample Description	Method / Analyte / Units / LOD	WEI-21 Recvd Wt. kg 0.02	ME-MS61 Ag ppm 0.01	ME-MS61 Al % 0.01	ME-MS61 As ppm 0.2	ME-MS61 Ba ppm 10	ME-MS61 Be ppm 0.05	ME-MS61 Bi ppm 0.01	ME-MS61 Ca % 0.01	ME-MS61 Cd ppm 0.02	ME-MS61 Ce ppm 0.01	ME-MS61 Co ppm 0.1	ME-MS61 Cr ppm 1	ME-MS61 Cs ppm 0.05	ME-MS61 Cu ppm 0.2	ME-MS61 Fe % 0.01
9359		0.87	0.07	6.72	6.9	2520	3.74	0.26	3.53	0.13	80.1	20.5	113	8.67	59.8	5.11
9360		0.88	0.06	6.95	10.1	2810	4.05	0.34	3.14	0.10	84.5	22.8	117	9.52	42.7	5.29
9361		0.06	>100	4.31	705	90	0.89	58.3	0.63	25.4	31.9	10.0	33	2.69	5180	2.26
9362		1.22	0.16	6.43	12.4	1650	2.86	1.64	4.58	0.02	76.7	17.9	96	4.34	18.9	4.16
9363		2.37	0.07	5.75	21.2	1600	1.50	0.33	2.85	0.05	63.1	11.2	74	1.68	23.4	3.24
9364		1.86	0.06	6.41	18.2	1700	1.96	0.31	1.60	0.18	74.2	10.6	73	1.71	28.0	3.26
9365		2.20	0.15	6.58	4.9	2150	3.95	0.56	5.90	0.51	85.4	18.7	85	1.13	37.8	5.38
9366		1.78	0.08	5.68	4.0	1230	2.43	0.26	2.91	0.55	58.6	12.0	71	1.48	27.7	2.98
9367		1.26	0.11	6.86	2.5	1620	3.10	0.23	0.38	0.69	79.7	10.6	89	1.84	20.7	2.78
9368		1.80	0.06	5.99	2.2	1360	2.15	0.33	1.43	0.29	55.5	12.1	83	2.53	30.9	3.05
9369		1.72	0.04	6.16	1.6	970	2.39	0.49	3.92	0.02	79.3	12.8	79	3.38	21.5	4.07
9370		1.93	0.04	6.41	1.8	1510	2.90	0.38	3.60	<0.02	76.2	15.0	82	4.09	51.5	4.07
9371		1.81	0.12	6.45	7.2	1010	2.00	0.44	0.70	0.88	91.3	19.9	83	2.65	20.5	3.19
9372		1.63	0.20	6.88	8.0	1450	2.00	0.44	0.56	3.16	95.8	35.6	77	4.29	83.6	3.84
9373		1.75	0.18	6.50	13.1	810	1.56	0.53	1.34	7.62	65.7	51.8	78	3.81	40.9	3.14
9374		1.95	0.10	7.63	16.2	2890	3.52	0.19	0.83	0.45	80.9	19.9	112	16.80	40.1	5.15
9375		1.01	0.01	0.07	0.8	20	0.09	0.02	32.5	0.05	1.18	2.2	2	0.08	3.4	0.11
9376		1.99	0.22	6.28	7.6	2950	3.15	0.33	4.82	0.12	165.0	18.4	82	1.57	58.8	4.75
9377		1.71	0.18	6.00	34.2	5600	4.43	1.07	2.02	0.23	149.5	21.5	65	4.25	18.3	2.55
9378		1.49	0.24	4.86	13.2	2000	1.32	2.25	1.18	0.29	131.0	10.3	27	6.19	41.6	2.37
9379		1.33	0.43	4.80	19.4	2310	1.14	2.81	0.98	0.37	125.0	20.6	32	3.48	124.0	2.45
9380		1.34	0.58	4.55	41.0	1720	0.92	8.09	1.97	0.31	119.0	34.9	29	0.74	123.0	2.31
9381		1.66	0.26	1.70	10.4	220	3.38	2.10	20.2	1.81	53.6	23.2	15	0.08	42.7	5.22
9382		1.54	0.07	4.53	17.0	2160	5.83	0.69	16.45	1.55	95.9	16.1	39	0.20	16.0	7.39
9383		1.79	0.14	5.45	12.8	4110	6.65	1.91	7.02	0.18	138.0	17.6	59	0.63	59.7	4.01
9384		1.97	0.84	0.67	5.1	220	1.48	14.20	29.4	0.96	49.7	5.8	4	<0.05	16.6	2.58
9385		1.88	1.81	0.38	4.9	120	0.67	24.7	33.2	3.44	54.9	5.0	2	0.06	30.6	2.09
9386		1.93	1.04	0.88	5.2	520	0.89	2.57	26.9	3.83	26.4	6.7	9	0.36	4.1	3.40
9387		1.88	0.01	0.56	4.2	70	0.99	0.04	28.3	0.09	9.64	2.2	3	0.19	7.3	1.20
9388		1.81	0.02	0.57	36.2	50	0.18	0.03	29.8	0.07	8.09	1.9	3	0.11	7.2	0.79
9389		1.85	0.01	0.79	30.1	40	0.83	0.02	30.4	0.06	13.45	4.1	6	0.10	14.2	1.25
9390		1.79	0.44	0.87	12.5	40	0.71	0.41	28.5	3.43	10.75	3.3	6	0.05	11.9	1.58
9391		1.90	0.03	0.80	5.7	110	0.73	0.03	30.2	0.13	8.62	3.4	6	0.54	17.4	0.76
9392		2.03	0.60	1.12	7.9	6140	1.52	0.91	29.2	2.08	17.10	5.3	8	0.96	2.9	0.94
9393		1.94	0.12	0.91	5.8	3600	0.93	0.23	32.6	0.74	15.75	5.3	6	0.96	8.4	0.52
9394		1.94	0.45	1.26	6.7	2180	0.93	0.76	29.7	3.52	24.2	4.9	10	0.57	20.0	0.70
9395		2.06	2.60	1.21	8.3	1770	0.90	4.30	16.55	8.44	29.0	4.4	19	0.14	12.8	0.41
9396		2.00	0.99	1.24	10.2	740	1.30	1.77	28.9	2.78	18.90	6.6	10	0.26	1.1	0.80
9397		1.92	0.47	1.18	7.4	840	0.89	1.60	30.5	0.88	13.00	5.5	7	3.44	19.3	0.81
9398		2.20	0.11	2.03	18.8	720	1.56	0.12	28.8	1.51	24.9	6.9	13	2.01	11.9	1.60

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 20-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18133994

Sample Description	Method / Analyte / Units / LOD	ME-MS61 Ga ppm 0.05	ME-MS61 Ge ppm 0.05	ME-MS61 Hf ppm 0.1	ME-MS61 In ppm 0.005	ME-MS61 K % 0.01	ME-MS61 La ppm 0.5	ME-MS61 Li ppm 0.2	ME-MS61 Mg % 0.01	ME-MS61 Mn ppm 5	ME-MS61 Mo ppm 0.05	ME-MS61 Na % 0.01	ME-MS61 Nb ppm 0.1	ME-MS61 Ni ppm 0.2	ME-MS61 P ppm 10	ME-MS61 Pb ppm 0.5
9359		19.55	0.15	4.3	0.077	4.03	41.0	16.4	1.89	1040	1.69	1.56	9.4	59.6	670	33.9
9360		21.8	0.18	4.5	0.082	3.91	42.6	19.2	2.06	1040	1.40	1.60	10.1	68.4	690	30.3
9361		21.6	0.15	2.7	5.27	0.66	15.9	22.4	0.20	232	4.50	0.44	7.7	60.2	590	1030
9362		16.85	0.16	5.1	0.082	4.08	39.9	11.2	1.27	900	2.02	1.49	8.3	36.4	620	12.2
9363		14.50	0.14	5.2	0.079	4.12	33.0	11.1	0.97	595	2.08	1.52	9.0	25.9	470	15.4
9364		16.80	0.15	4.8	0.052	4.07	40.1	13.3	1.14	537	1.60	2.00	9.9	27.7	440	34.2
9365		19.10	0.16	4.7	0.123	3.48	45.1	11.4	2.23	1190	2.22	1.64	9.9	47.4	640	128.0
9366		14.90	0.14	5.3	0.081	3.63	30.6	17.7	1.23	425	1.63	1.87	9.0	28.4	450	180.5
9367		18.55	0.14	5.9	0.024	4.02	42.6	19.3	1.23	254	2.73	2.20	11.0	36.8	520	306
9368		14.75	0.14	4.5	0.025	3.92	28.9	14.9	1.08	300	1.87	1.91	8.0	30.7	480	121.5
9369		16.85	0.17	4.9	0.052	2.80	42.6	20.8	1.28	459	2.04	2.38	9.2	32.8	530	13.1
9370		18.20	0.16	5.1	0.082	3.37	40.1	20.8	1.32	447	2.14	2.48	9.6	36.0	550	18.7
9371		16.05	0.16	5.5	0.024	3.36	48.7	22.2	1.31	242	1.91	2.55	9.5	27.7	530	151.0
9372		19.35	0.17	7.1	0.046	4.03	50.0	27.9	1.62	296	2.45	2.01	13.9	38.5	500	269
9373		17.30	0.14	5.2	0.097	3.82	34.1	18.6	1.34	314	2.70	2.59	11.1	37.9	450	414
9374		22.5	0.18	4.3	0.058	4.40	40.4	36.9	2.21	643	1.42	1.63	11.4	70.2	540	80.7
9375		0.47	0.09	0.1	<0.005	0.03	1.3	1.5	1.87	104	0.09	0.03	0.1	<0.2	70	5.9
9376		17.95	0.22	4.5	0.134	4.13	99.5	3.5	1.58	1810	2.26	1.41	9.5	43.6	510	85.4
9377		19.65	0.22	4.0	0.074	3.82	80.7	7.4	0.69	936	1.95	1.62	11.5	34.2	360	26.8
9378		13.20	0.17	3.0	0.122	3.70	72.3	10.1	0.44	776	2.73	1.36	9.1	9.1	230	40.4
9379		12.65	0.17	2.9	0.090	3.88	63.4	8.1	0.37	628	2.09	1.37	8.4	11.6	220	58.6
9380		11.35	0.15	2.5	0.162	3.41	55.2	4.1	0.23	478	2.16	1.47	7.4	18.8	210	64.5
9381		7.33	0.10	1.1	0.317	0.25	27.9	2.7	1.35	5260	0.79	0.18	2.6	14.9	70	23.4
9382		16.20	0.14	3.3	0.435	1.13	51.3	4.0	1.77	6690	1.15	0.76	8.7	21.6	280	14.4
9383		17.10	0.19	4.2	0.411	4.31	73.4	2.6	1.23	3100	2.05	0.99	10.6	29.1	360	14.4
9384		3.72	0.07	0.5	0.237	0.06	26.1	1.3	1.04	5490	0.38	0.03	1.1	6.1	50	67.0
9385		2.38	0.07	0.3	0.167	0.04	28.6	0.9	0.73	5770	0.06	0.02	0.5	1.8	30	129.5
9386		3.43	0.05	0.6	0.034	0.18	15.5	2.6	0.90	11650	0.77	0.02	1.2	7.3	70	137.0
9387		1.97	0.05	0.4	0.017	0.04	5.8	1.0	4.92	5890	0.15	0.01	0.9	2.8	30	2.5
9388		1.93	0.06	0.4	0.015	0.02	4.1	0.6	4.10	3830	0.07	<0.01	1.0	3.3	40	2.2
9389		2.56	0.05	0.5	0.014	0.01	7.4	1.0	4.47	3940	0.14	<0.01	1.3	7.6	50	5.0
9390		2.61	0.06	0.6	0.018	<0.01	5.2	0.9	5.18	3560	<0.05	<0.01	1.4	5.3	60	923
9391		2.54	0.07	0.5	0.011	0.09	4.4	1.3	4.03	3150	<0.05	<0.01	1.4	5.3	40	13.9
9392		3.88	0.07	0.8	0.016	0.41	10.1	6.8	1.65	6880	1.13	<0.01	1.8	9.2	70	172.5
9393		2.85	0.07	0.7	0.011	0.30	9.0	7.5	1.59	5000	0.09	<0.01	1.4	6.6	60	42.9
9394		3.59	0.09	0.9	0.018	0.48	13.2	3.6	0.95	6970	0.28	0.01	1.9	6.4	100	240
9395		2.76	0.11	0.7	0.022	1.19	18.1	1.6	0.43	4200	1.46	0.02	1.8	4.5	70	984
9396		4.02	0.08	0.9	0.031	0.18	10.3	4.7	1.35	10400	0.32	0.01	2.0	6.4	50	311
9397		3.19	0.09	0.8	0.020	0.80	6.7	6.1	2.56	4220	0.12	0.01	1.9	9.4	70	51.3
9398		6.15	0.09	1.4	0.032	0.45	12.9	6.6	2.95	5830	0.15	0.01	3.3	17.1	60	14.7

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 20-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18133994

Sample Description	Method / Analyte / Units / LOD	ME-MS61 Rb ppm 0.1	ME-MS61 Re ppm 0.002	ME-MS61 S % 0.01	ME-MS61 Sb ppm 0.05	ME-MS61 Sc ppm 0.1	ME-MS61 Se ppm 1	ME-MS61 Sn ppm 0.2	ME-MS61 Sr ppm 0.2	ME-MS61 Ta ppm 0.05	ME-MS61 Te ppm 0.05	ME-MS61 Th ppm 0.01	ME-MS61 Ti % 0.005	ME-MS61 Tl ppm 0.02	ME-MS61 U ppm 0.1	ME-MS61 V ppm 1
9359		238	0.003	0.12	0.30	15.7	1	2.9	124.5	0.82	<0.05	13.00	0.328	2.44	4.9	99
9360		226	0.002	0.11	0.33	17.7	1	2.7	126.0	0.86	0.05	13.75	0.345	2.66	5.1	107
9361		26.7	<0.002	2.12	87.7	4.3	34	5.8	451	0.63	40.8	6.94	0.216	1.76	2.6	32
9362		225	0.002	0.08	0.38	11.2	1	2.8	110.0	0.75	0.09	13.10	0.267	1.61	5.2	69
9363		182.0	<0.002	0.13	0.32	7.4	1	2.4	83.7	0.82	0.06	16.05	0.216	1.02	5.7	42
9364		174.0	0.002	0.14	0.26	8.0	1	1.9	69.1	0.87	<0.05	14.40	0.227	1.01	5.4	49
9365		147.0	0.002	0.25	0.79	13.4	1	3.8	202	0.87	<0.05	15.40	0.288	0.72	5.7	79
9366		134.5	<0.002	0.19	0.28	7.4	1	2.7	60.9	0.82	<0.05	17.50	0.211	0.67	6.2	42
9367		150.5	0.002	0.15	0.22	9.9	1	1.8	47.2	0.98	<0.05	16.90	0.270	1.01	6.3	62
9368		156.5	<0.002	0.23	0.20	8.4	1	1.4	65.5	0.71	<0.05	11.55	0.222	0.92	4.3	51
9369		161.0	<0.002	0.14	0.18	10.7	<1	2.0	142.5	0.79	<0.05	14.70	0.247	0.92	5.3	64
9370		178.5	0.002	0.11	0.18	11.1	1	2.5	133.5	0.83	<0.05	16.05	0.253	1.14	5.8	63
9371		122.5	<0.002	0.31	0.25	8.1	1	1.2	37.0	0.83	<0.05	15.70	0.236	0.79	5.9	48
9372		173.0	0.003	0.52	0.41	9.4	1	2.2	33.5	1.17	0.07	20.4	0.256	1.12	7.5	51
9373		153.0	0.003	0.59	0.40	9.3	1	1.7	27.8	0.93	0.10	16.35	0.248	1.13	6.0	55
9374		292	0.003	0.22	0.30	18.3	1	2.3	75.3	0.94	0.05	15.05	0.346	2.82	4.7	109
9375		1.4	<0.002	<0.01	0.12	0.3	1	<0.2	79.3	<0.05	<0.05	0.13	0.005	0.02	0.1	1
9376		145.0	0.003	0.26	0.53	12.1	1	4.9	97.4	0.79	<0.05	16.20	0.259	0.78	5.2	89
9377		155.5	0.003	0.08	0.34	9.6	1	2.6	56.3	0.92	<0.05	17.85	0.223	1.07	5.5	55
9378		194.5	<0.002	0.16	0.27	3.6	1	1.6	40.5	0.69	<0.05	27.8	0.135	1.24	4.8	23
9379		167.5	<0.002	0.53	0.32	3.6	1	1.7	39.1	0.61	<0.05	24.8	0.129	0.96	4.7	21
9380		116.0	0.002	1.03	0.40	2.9	2	2.1	69.6	0.53	0.09	23.5	0.108	0.63	4.0	16
9381		7.0	<0.002	0.33	0.48	3.0	1	7.8	133.0	0.21	0.20	4.38	0.057	0.05	1.6	17
9382		35.4	<0.002	0.12	0.89	8.7	1	11.1	129.5	0.69	<0.05	10.95	0.179	0.21	4.3	46
9383		148.5	<0.002	0.23	0.87	11.5	1	6.3	108.0	0.82	0.05	11.80	0.231	0.83	4.0	65
9384		1.9	<0.002	0.04	0.26	1.3	2	1.6	110.0	0.09	0.64	1.50	0.022	0.03	0.7	6
9385		2.4	<0.002	0.16	0.17	0.6	2	0.9	101.5	0.05	0.97	0.95	0.010	0.05	0.3	3
9386		11.1	<0.002	0.04	0.35	1.5	1	0.7	109.0	0.08	0.15	1.75	0.032	0.13	1.2	10
9387		3.3	<0.002	0.06	0.32	1.1	1	0.3	151.0	0.07	<0.05	1.13	0.023	0.04	0.9	6
9388		1.4	<0.002	0.07	0.40	1.3	1	<0.2	179.5	0.07	0.05	1.21	0.025	0.03	1.0	7
9389		0.9	<0.002	0.12	0.50	1.6	1	0.2	180.0	0.11	<0.05	1.83	0.034	0.03	1.2	9
9390		0.6	<0.002	0.12	0.77	1.7	1	0.4	172.0	0.10	<0.05	1.89	0.035	0.02	1.2	10
9391		9.0	<0.002	0.09	0.33	1.6	1	0.3	177.0	0.11	<0.05	1.86	0.034	0.09	1.0	10
9392		26.7	<0.002	0.01	0.34	2.1	1	0.4	154.0	0.14	<0.05	2.48	0.046	0.21	1.2	12
9393		27.8	<0.002	0.03	0.34	2.0	1	0.3	201	0.13	<0.05	2.16	0.038	0.17	1.2	10
9394		23.3	<0.002	0.04	0.47	2.6	1	0.5	124.0	0.16	<0.05	3.77	0.051	0.12	1.6	14
9395		31.5	<0.002	0.09	0.63	2.2	1	0.6	61.4	0.15	0.12	2.31	0.046	0.18	1.9	12
9396		8.2	<0.002	0.02	0.67	2.3	1	0.9	124.5	0.17	0.07	3.14	0.048	0.07	1.3	13
9397		85.2	<0.002	0.04	0.26	2.1	2	0.5	164.0	0.15	0.10	2.84	0.046	0.47	1.6	12
9398		45.6	<0.002	0.04	0.48	3.8	1	0.9	138.5	0.27	0.05	5.74	0.083	0.27	1.7	21

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 20-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18133994

Sample Description	Method / Analyte / Units / LOD	ME-MS61 W ppm 0.1	ME-MS61 Y ppm 0.1	ME-MS61 Zn ppm 2	ME-MS61 Zr ppm 0.5	Ag-OG62 Ag ppm 1	Cu-OG62 Cu % 0.001	Ni-OG62 Ni % 0.001	CRU-QC Pass2mm % 0.01	PUL-QC Pass75um % 0.01
9359		0.8	22.7	89	151.0					
9360		1.1	23.7	82	156.5					
9361		13.3	6.1	4290	88.3	116				
9362		0.9	19.6	45	183.5					
9363		0.7	16.5	36	189.5					
9364		0.6	17.6	67	170.0					
9365		1.0	26.1	189	165.5					
9366		0.7	17.1	114	194.0					
9367		1.6	18.3	128	205					
9368		0.5	14.2	76	161.5					
9369		0.6	22.7	28	178.5					
9370		0.9	22.3	30	185.0					
9371		0.9	16.0	161	198.5					
9372		1.5	21.7	314	250					
9373		1.1	17.0	709	179.5					
9374		3.0	22.3	255	151.5					
9375		<0.1	2.0	9	2.4					
9376		1.1	28.8	115	157.0					
9377		0.8	20.7	102	138.0					
9378		0.4	11.2	103	106.5					
9379		0.4	9.5	98	98.1					
9380		0.3	8.9	57	86.6					
9381		0.5	16.8	352	39.3					
9382		0.6	28.3	363	113.5					
9383		0.8	23.8	129	144.5					
9384		0.4	10.1	218	16.0					
9385		0.6	27.1	606	8.3					
9386		0.5	7.3	643	24.4					
9387		0.2	4.9	30	13.9					
9388		0.1	5.4	19	13.2					
9389		0.1	5.6	23	20.7				89.8	
9390		0.3	5.6	468	20.5					
9391		0.3	4.5	31	19.7					
9392		0.1	6.4	377	26.9					
9393		<0.1	6.9	152	25.4					
9394		0.1	13.0	639	31.2					
9395		0.2	7.8	1460	27.3					
9396		0.1	11.3	610	30.4					
9397		<0.1	6.0	186	27.6					
9398		0.1	7.1	336	49.2				90.9	92.2

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 20-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18133994

Sample Description	Method / Analyte / Units / LOD	WEI-21 Recvd Wt. kg 0.02	ME-MS61 Ag ppm 0.01	ME-MS61 Al % 0.01	ME-MS61 As ppm 0.2	ME-MS61 Ba ppm 10	ME-MS61 Be ppm 0.05	ME-MS61 Bi ppm 0.01	ME-MS61 Ca % 0.01	ME-MS61 Cd ppm 0.02	ME-MS61 Ce ppm 0.01	ME-MS61 Co ppm 0.1	ME-MS61 Cr ppm 1	ME-MS61 Cs ppm 0.05	ME-MS61 Cu ppm 0.2	ME-MS61 Fe % 0.01
9399		0.86	0.10	2.55	17.4	640	1.83	0.21	29.1	0.36	29.2	5.8	16	2.41	6.5	1.70
9400		0.97	0.17	2.47	16.4	630	1.78	0.38	28.5	0.27	30.6	5.6	17	2.55	7.0	1.65
9401		0.07	3.98	5.35	14.2	110	0.54	0.84	3.41	2.01	15.45	953	264	0.71	>10000	17.40
9402		2.24	0.23	3.76	44.5	130	2.36	0.46	26.0	4.36	52.2	9.6	34	0.05	6.2	3.05
9403		1.46	0.31	5.90	36.6	980	1.78	1.01	18.60	3.26	85.5	15.0	48	0.09	3.0	5.90
9404		1.67	0.27	6.78	46.1	4010	3.24	0.71	10.55	4.08	155.5	24.7	56	0.34	120.5	4.39
9405		1.71	0.47	2.51	61.2	430	0.51	1.09	0.39	0.34	34.1	22.3	30	0.29	337	1.25
9406		1.44	0.31	2.95	20.2	290	0.56	0.24	0.32	0.13	52.8	12.5	56	0.11	345	1.05
9407		1.96	0.50	5.55	46.4	790	1.65	0.39	0.85	0.27	182.5	29.0	73	0.68	408	2.14
9408		2.04	0.12	7.21	10.0	430	1.48	0.33	6.35	0.07	15.85	38.7	49	2.38	97.3	8.21
9409		2.09	0.11	7.55	16.8	280	0.52	0.21	7.14	0.08	18.60	45.9	49	1.51	135.5	8.31
9410		1.96	0.09	7.56	3.4	180	0.53	0.09	7.21	0.07	17.90	49.6	39	1.02	139.0	8.44
9411		2.25	0.11	7.12	3.4	240	0.72	0.14	6.68	0.10	69.8	45.7	26	0.74	117.5	9.42
9412		2.14	0.14	7.12	2.5	330	0.74	0.12	5.97	0.10	26.3	49.7	12	1.04	153.5	10.05
9413		2.32	0.08	6.92	2.8	260	0.79	0.21	6.69	0.07	26.4	44.9	8	0.56	115.0	9.83
9414		2.26	0.06	6.59	2.9	330	0.85	0.31	5.18	0.11	23.4	52.2	4	0.55	112.0	10.75
9415		2.10	0.14	6.99	1.3	280	0.92	0.61	5.15	0.08	23.7	59.2	4	0.82	180.5	10.70
9416		2.13	0.16	6.66	1.5	220	0.80	0.61	6.15	0.05	23.0	67.7	4	0.85	504	9.97
9417		2.05	0.10	6.64	2.2	370	0.95	0.65	4.96	0.07	27.4	61.8	4	1.46	166.5	11.35
9418		2.27	0.15	6.75	1.6	250	0.79	0.55	7.83	0.10	23.0	54.3	5	0.99	188.5	11.00
9419		2.33	0.10	6.78	3.9	190	0.83	0.28	5.58	0.11	25.4	55.9	4	0.70	147.0	11.60
9420		2.25	0.03	6.06	4.6	260	0.97	0.19	5.10	0.10	37.0	57.1	2	0.94	81.1	12.50
9421		2.49	0.03	5.99	2.2	330	1.09	0.21	4.96	0.07	45.1	45.5	2	1.15	68.3	10.75
9422		2.22	0.08	6.10	4.9	270	0.80	0.19	4.23	0.13	37.8	54.2	3	0.66	107.0	12.15

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 20-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18133994

Sample Description	Method / Analyte / Units / LOD	ME-MS61 Ga ppm 0.05	ME-MS61 Ge ppm 0.05	ME-MS61 Hf ppm 0.1	ME-MS61 In ppm 0.005	ME-MS61 K % 0.01	ME-MS61 La ppm 0.5	ME-MS61 Li ppm 0.2	ME-MS61 Mg % 0.01	ME-MS61 Mn ppm 5	ME-MS61 Mo ppm 0.05	ME-MS61 Na % 0.01	ME-MS61 Nb ppm 0.1	ME-MS61 Ni ppm 0.2	ME-MS61 P ppm 10	ME-MS61 Pb ppm 0.5
9399		6.78	0.09	1.8	0.035	0.51	15.8	8.4	2.78	6430	0.29	0.02	4.5	16.3	110	13.2
9400		6.54	0.09	1.6	0.026	0.54	17.1	7.7	2.75	6070	0.31	0.01	4.1	17.2	90	20.4
9401		11.15	0.33	1.2	0.126	0.31	7.2	9.4	3.94	995	4.45	1.15	4.8	>10000	450	13.2
9402		10.45	0.08	3.5	0.062	0.08	25.1	3.5	2.01	12250	0.18	0.02	6.0	32.0	220	79.1
9403		17.10	0.11	4.9	0.248	0.63	49.6	1.5	1.58	8980	1.92	0.70	11.4	38.9	240	32.9
9404		17.85	0.21	5.5	0.149	4.32	93.5	2.6	1.59	4370	1.15	0.42	12.0	45.0	390	23.8
9405		5.31	0.11	1.2	0.028	1.42	18.6	4.7	0.28	148	1.77	0.96	2.2	13.1	100	105.5
9406		6.01	0.13	2.5	0.024	1.24	29.1	4.6	0.26	100	2.12	1.42	3.5	9.6	190	29.3
9407		13.80	0.23	3.5	0.057	1.90	113.0	9.4	0.67	226	2.26	2.66	6.9	29.3	350	42.8
9408		16.65	0.12	1.5	0.109	1.17	7.6	18.6	4.00	1360	0.63	1.82	3.0	81.2	310	7.2
9409		17.05	0.10	1.6	0.064	0.87	9.2	14.6	4.00	1370	0.66	1.58	3.0	86.1	330	5.8
9410		18.10	0.12	1.9	0.068	0.63	8.6	12.1	4.05	1440	0.69	1.72	3.3	86.1	350	4.2
9411		19.15	0.11	2.3	0.144	0.62	41.3	11.0	3.56	1730	0.73	1.97	4.7	65.6	420	5.9
9412		19.80	0.11	2.5	0.085	1.09	12.7	9.9	3.02	1740	0.93	1.85	4.7	53.3	510	6.7
9413		18.85	0.11	2.5	0.131	0.79	13.3	8.0	3.08	1730	0.73	2.07	4.6	47.9	450	6.9
9414		18.40	0.10	2.2	0.081	0.64	11.3	11.2	2.90	1610	0.50	2.23	4.6	41.8	460	6.7
9415		20.2	0.10	2.3	0.099	0.83	11.5	12.3	3.01	1530	2.12	2.19	4.5	47.2	450	6.9
9416		20.6	0.11	2.6	0.089	0.76	11.7	11.7	2.70	1420	5.17	2.16	4.5	52.3	460	3.7
9417		20.7	0.11	2.6	0.089	1.25	13.3	12.7	2.83	1560	0.81	1.94	5.2	40.8	490	3.6
9418		20.1	0.12	2.3	0.095	0.84	10.9	11.0	2.81	1660	0.99	1.77	4.3	44.6	440	2.9
9419		20.0	0.09	2.4	0.078	0.68	12.3	7.9	2.40	1700	0.70	1.87	4.5	29.2	490	5.1
9420		23.3	0.10	3.5	0.092	0.85	17.8	10.3	1.86	1760	7.34	2.24	6.9	15.6	660	4.0
9421		21.9	0.15	4.1	0.095	1.15	20.6	9.0	1.53	1520	9.97	2.36	7.7	8.3	850	3.7
9422		20.4	0.13	3.5	0.108	1.00	16.5	5.8	1.79	1680	1.25	2.19	6.5	13.7	680	6.8

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 20-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18133994

Sample Description	Method / Analyte / Units / LOD	ME-MS61 Rb ppm 0.1	ME-MS61 Re ppm 0.002	ME-MS61 S % 0.01	ME-MS61 Sb ppm 0.05	ME-MS61 Sc ppm 0.1	ME-MS61 Se ppm 1	ME-MS61 Sn ppm 0.2	ME-MS61 Sr ppm 0.2	ME-MS61 Ta ppm 0.05	ME-MS61 Te ppm 0.05	ME-MS61 Th ppm 0.01	ME-MS61 Ti % 0.005	ME-MS61 Tl ppm 0.02	ME-MS61 U ppm 0.1	ME-MS61 V ppm 1
9399		56.1	<0.002	0.02	0.76	4.5	1	1.0	145.0	0.37	<0.05	5.92	0.104	0.27	2.2	28
9400		58.9	<0.002	0.02	0.59	4.2	1	0.9	141.5	0.33	<0.05	5.22	0.099	0.27	1.9	27
9401		10.4	0.049	8.33	3.08	8.2	22	2.5	177.0	0.31	4.01	1.07	0.512	0.17	0.3	78
9402		2.5	<0.002	0.06	3.12	6.3	<1	1.6	81.9	0.55	0.05	9.30	0.149	<0.02	2.8	35
9403		17.2	<0.002	0.04	0.40	9.5	<1	2.3	129.5	0.86	0.05	12.80	0.227	0.07	3.5	49
9404		111.0	<0.002	0.10	0.89	11.0	<1	2.1	237	0.97	<0.05	18.95	0.264	0.35	6.3	69
9405		45.0	<0.002	0.21	0.24	1.8	1	0.4	15.0	0.20	<0.05	5.31	0.055	0.38	2.3	12
9406		31.6	<0.002	0.13	0.23	2.8	<1	0.6	12.1	0.30	<0.05	11.75	0.100	0.16	3.9	19
9407		50.7	<0.002	0.25	0.24	8.3	1	1.2	42.9	0.56	<0.05	13.70	0.197	0.30	8.5	61
9408		81.3	<0.002	0.08	0.67	34.0	<1	1.0	192.0	0.21	<0.05	1.97	0.490	0.76	0.7	244
9409		54.1	<0.002	0.09	0.48	34.3	1	0.8	186.5	0.23	<0.05	2.06	0.521	0.57	0.6	255
9410		36.6	<0.002	0.10	0.41	36.6	1	0.9	194.5	0.23	0.07	2.13	0.538	0.24	0.6	265
9411		30.0	<0.002	0.09	0.73	34.5	1	1.3	219	0.30	<0.05	3.00	0.603	0.18	1.5	266
9412		55.5	<0.002	0.11	0.49	35.3	1	1.2	193.0	0.33	<0.05	3.26	0.710	0.27	0.9	304
9413		35.6	<0.002	0.11	0.64	34.8	1	1.2	221	0.34	0.05	3.17	0.721	0.19	1.0	310
9414		26.8	<0.002	0.14	0.54	37.6	1	1.1	161.0	0.34	<0.05	2.77	0.882	0.14	0.8	379
9415		36.9	0.004	0.18	0.45	37.1	1	1.2	152.5	0.33	<0.05	3.12	0.874	0.20	1.4	412
9416		33.5	0.016	0.33	0.45	31.7	1	1.1	135.5	0.33	0.05	3.13	0.886	0.20	2.1	383
9417		59.9	0.003	0.18	0.45	37.8	<1	1.3	142.5	0.38	0.06	3.43	0.965	0.33	1.0	438
9418		39.9	0.002	0.14	0.40	37.7	1	1.1	182.0	0.32	<0.05	2.79	0.877	0.22	0.8	435
9419		29.8	0.002	0.14	0.57	36.2	1	1.2	195.5	0.33	<0.05	3.22	0.948	0.16	0.9	458
9420		34.9	0.003	0.18	0.28	37.1	1	1.5	91.1	0.50	<0.05	4.27	1.310	0.18	1.6	468
9421		45.8	<0.002	0.17	0.26	33.2	1	1.5	125.5	0.55	0.07	5.03	0.998	0.23	2.6	236
9422		35.0	<0.002	0.17	0.54	33.3	1	1.6	171.0	0.46	<0.05	4.07	1.010	0.16	1.3	362

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 20-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18133994

Sample Description	Method / Analyte / Units / LOD	ME-MS61 W ppm 0.1	ME-MS61 Y ppm 0.1	ME-MS61 Zn ppm 2	ME-MS61 Zr ppm 0.5	Ag-OG62 Ag ppm 1	Cu-OG62 Cu % 0.001	Ni-OG62 Ni % 0.001	CRU-QC Pass2mm % 0.01	PUL-QC Pass75um % 0.01
9399		0.2	8.1	122	63.8					94.9
9400		0.2	8.1	94	60.5					95.8
9401		2.2	9.3	138	45.5		1.600	4.47		
9402		0.6	18.4	1430	125.0					
9403		0.4	21.8	910	173.0				79.0	
9404		0.4	25.1	1200	190.0					
9405		0.2	3.5	94	41.5					
9406		0.3	5.6	31	92.5					
9407		0.5	12.6	69	131.0					
9408		0.4	16.0	107	51.2					
9409		0.3	16.3	101	56.5					
9410		0.4	18.0	102	62.8					
9411		0.5	22.3	126	85.6					
9412		0.4	22.8	128	93.7					
9413		0.5	22.4	121	100.0					
9414		0.6	21.0	122	80.1					
9415		0.6	20.8	118	88.0					
9416		0.8	18.4	121	93.5					
9417		0.7	24.4	119	97.2					
9418		0.7	21.2	132	79.1					
9419		0.6	22.3	136	91.7					
9420		0.9	30.5	126	128.5					
9421		0.7	33.8	111	151.0					
9422		0.7	30.7	150	126.5					

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 20-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18133994

CERTIFICATE COMMENTS

ANALYTICAL COMMENTS

REE's may not be totally soluble in this method.

Applies to Method: ME-MS61

LABORATORY ADDRESSES

Processed at ALS Sudbury located at 1351-B Kelly Lake Road, Unit #1, Sudbury, ON, Canada.

Applies to Method:

CRU-31	CRU-QC	LOG-22	LOG-24
PUL-31	PUL-QC	SPL-21	WEI-21

Processed at ALS Vancouver located at 2103 Dollarton Hwy, North Vancouver, BC, Canada.

Applies to Method:

Ag-OG62	Cu-OG62	ME-MS61	ME-OG62
Ni-OG62			