ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 9-JUN-2018
This copy reported on
14-JUN-2018
Account: BMRPLLBW

CERTIFICATE SD18125489

Project: Iron Mask

This report is for 82 Drill Core samples submitted to our lab in Sudbury, ON, Canada on 29-MAY-2018.

The following have access to data associated with this certificate:

SANDY DE LA MARE	PETER DOYLE	JON EDWARDS
MIKE HENDRICKSON	FRANK PLOEGER	IAN PRINGLE
MERCEDES RICH	CLYDE SMITH	

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
LOG-24	Pulp Login - Rcd w/o Barcode
CRU-31	Fine crushing - 70% <2mm
CRU-QC	Crushing QC Test
PUL-QC	Pulverizing QC Test
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
ME-OG62	Ore Grade Elements - Four Acid	ICP-AES
Cu-OG62	Ore Grade Cu - Four Acid	ICP-AES
Ni-OG62	Ore Grade Ni - Four Acid	ICP-AES
ME-MS61	48 element four acid ICP-MS	
Ag-OG62	Ore Grade Ag - Four Acid	ICP-AES

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

***** See Appendix Page for comments regarding this certificate *****

Comments: ***Corrected copy with project name McAra corrected to Iron Mask***

Signature:

Colin Ramshaw, Vancouver Laboratory Manager

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 9-JUN-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18125489

Sample Description	Method / Analyte / Units / LOD	WEI-21 Recvd Wt. kg 0.02	ME-MS61 Ag ppm 0.01	ME-MS61 Al % 0.01	ME-MS61 As ppm 0.2	ME-MS61 Ba ppm 10	ME-MS61 Be ppm 0.05	ME-MS61 Bi ppm 0.01	ME-MS61 Ca % 0.01	ME-MS61 Cd ppm 0.02	ME-MS61 Ce ppm 0.01	ME-MS61 Co ppm 0.1	ME-MS61 Cr ppm 1	ME-MS61 Cs ppm 0.05	ME-MS61 Cu ppm 0.2	ME-MS61 Fe % 0.01
14001		1.52	0.01	7.41	1.4	210	1.75	0.19	0.34	<0.02	50.9	16.4	100	0.87	2.3	3.96
14002		1.53	0.01	7.23	1.2	100	1.83	0.11	0.22	<0.02	24.3	10.3	89	0.29	1.8	3.68
14003		1.45	<0.01	6.79	0.8	80	2.50	0.03	0.18	<0.02	35.0	6.6	68	0.22	1.0	3.13
14004		2.07	0.01	6.20	32.6	50	1.39	0.43	0.59	<0.02	20.5	55.7	62	0.25	6.8	3.87
14005		2.12	0.12	7.03	4.9	190	2.22	0.11	0.33	0.02	30.2	13.5	64	0.79	3.1	3.59
14006		2.13	0.01	6.02	3.5	20	1.05	0.16	0.91	<0.02	19.20	50.7	46	0.09	1.4	2.51
14007		2.09	0.01	6.67	6.4	50	1.34	0.22	0.22	<0.02	61.8	58.9	77	0.32	2.9	4.35
14008		2.09	<0.01	6.07	3.7	80	1.33	0.07	0.55	<0.02	14.90	22.0	57	0.32	2.0	3.57
14009		2.27	<0.01	7.06	5.9	130	2.31	0.16	0.69	<0.02	41.7	18.1	78	0.43	3.3	3.27
14010		2.16	0.02	5.99	24.4	20	0.97	0.52	1.13	<0.02	16.10	70.7	51	0.10	3.1	2.04
14011		2.18	0.01	6.38	3.4	40	1.34	0.05	0.49	<0.02	9.30	8.7	50	0.17	1.5	2.32
14012		2.32	0.01	6.77	25.0	130	1.44	0.45	1.18	<0.02	30.8	12.6	63	0.39	46.6	3.26
14013		2.25	0.02	6.69	7.4	110	1.28	0.51	0.89	<0.02	55.4	31.1	83	0.55	26.1	4.29
14014		2.02	0.02	6.63	10.3	80	1.37	0.27	0.69	<0.02	19.50	30.2	76	0.36	4.1	3.94
14015		2.14	0.07	6.34	11.3	110	1.27	0.69	0.75	<0.02	164.5	63.4	85	0.55	1265	6.24
14016		2.16	0.02	5.60	8.9	80	1.60	0.27	1.23	<0.02	17.85	32.4	84	0.34	8.9	2.64
14017		2.14	<0.01	6.51	2.5	150	1.78	0.07	0.24	<0.02	18.75	25.7	107	0.61	4.0	3.07
14018		1.57	0.02	7.12	4.8	200	1.96	0.20	0.33	<0.02	20.7	24.1	107	0.60	4.6	4.06
14019		1.95	0.04	6.21	26.7	300	1.60	0.82	1.25	0.04	66.6	20.5	172	0.98	43.5	3.39
14020		1.49	0.02	6.35	14.6	510	1.43	0.57	1.28	<0.02	14.90	10.7	65	0.68	5.9	2.02
14021		1.78	0.02	5.79	16.8	810	1.87	0.92	0.25	0.03	26.4	41.1	50	0.86	24.8	3.93
14022		2.01	0.02	6.33	4.8	510	1.16	0.09	1.34	<0.02	23.5	5.9	64	0.52	4.8	1.64
14023		2.21	0.02	6.55	3.1	1920	2.03	1.99	1.78	0.02	53.3	6.1	55	1.04	17.4	1.96
14024		2.04	0.03	6.23	6.8	1040	1.51	0.73	2.14	<0.02	45.9	12.0	60	0.96	27.6	2.01
14025		1.07	<0.01	0.06	<0.2	20	<0.05	0.01	32.6	0.02	0.97	1.0	2	<0.05	1.4	0.07
14026		1.94	0.04	6.82	28.1	210	1.59	1.70	0.90	<0.02	46.2	33.0	90	1.04	12.3	3.35
14027		2.09	0.04	6.89	23.8	200	1.45	1.50	0.71	0.02	56.0	29.4	86	1.22	46.0	4.68
14028		2.15	0.05	6.52	14.4	200	2.38	1.41	1.02	0.02	138.5	46.0	71	1.15	8.5	3.63
14029		2.07	0.02	6.72	6.9	340	1.86	0.32	1.76	<0.02	34.4	14.3	72	0.70	2.8	2.64
14030		2.12	0.01	6.18	5.7	410	1.63	0.29	0.86	<0.02	27.8	12.4	55	0.89	2.4	3.00
14031		2.12	0.02	6.31	4.0	360	1.31	0.35	1.24	0.02	20.7	20.2	67	0.74	1.8	3.43
14032		2.30	0.02	6.19	5.0	300	1.83	0.44	0.57	<0.02	64.1	10.1	79	1.23	3.8	2.59
14033		2.34	0.16	6.04	78.8	300	1.75	5.39	1.98	<0.02	45.6	89.6	60	1.70	41.4	5.78
14034		1.86	0.03	6.49	6.7	660	1.69	0.43	1.42	<0.02	27.2	7.9	57	0.82	5.9	1.98
14057		1.99	0.01	6.16	1.4	90	1.15	0.18	0.21	<0.02	102.0	8.7	67	0.53	10.4	1.67
14035		2.06	0.02	7.22	1.8	350	1.55	0.26	0.24	0.03	53.0	21.7	77	1.34	1.5	3.60
14036		2.05	0.02	5.65	2.9	10	0.61	0.25	0.15	<0.02	18.65	30.0	53	0.06	2.0	3.26
14037		1.90	0.01	7.83	2.6	470	2.10	0.24	0.38	0.03	57.2	27.3	115	1.73	4.4	4.09
14038		2.04	0.01	6.34	1.4	200	1.39	0.17	0.27	<0.02	16.95	14.5	86	0.52	4.3	3.32
14039		0.81	0.02	7.91	1.3	580	2.30	0.32	0.47	<0.02	77.2	17.3	114	1.77	31.9	4.20

Comments: ***Corrected copy with project name McAra corrected to Iron Mask***

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 9-JUN-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18125489

Sample Description	Method / Analyte / Units / LOD	ME-MS61 Ga ppm 0.05	ME-MS61 Ge ppm 0.05	ME-MS61 Hf ppm 0.1	ME-MS61 In ppm 0.005	ME-MS61 K % 0.01	ME-MS61 La ppm 0.5	ME-MS61 Li ppm 0.2	ME-MS61 Mg % 0.01	ME-MS61 Mn ppm 5	ME-MS61 Mo ppm 0.05	ME-MS61 Na % 0.01	ME-MS61 Nb ppm 0.1	ME-MS61 Ni ppm 0.2	ME-MS61 P ppm 10	ME-MS61 Pb ppm 0.5
14001		19.15	0.15	3.1	0.020	0.89	25.4	12.4	1.64	198	1.69	3.90	5.6	42.1	510	4.4
14002		17.05	0.16	2.9	0.010	0.43	12.6	10.5	1.42	181	1.41	4.30	4.7	36.4	460	3.3
14003		15.95	0.14	2.2	0.010	0.39	17.2	8.7	1.13	147	1.03	4.34	3.3	27.7	370	2.6
14004		13.40	0.12	1.9	0.011	0.34	10.2	6.5	0.80	150	1.41	4.12	2.8	23.3	280	4.3
14005		18.00	0.15	2.0	0.026	0.87	15.1	13.4	1.59	185	0.79	3.66	3.5	36.9	370	3.6
14006		11.00	0.13	1.2	<0.005	0.15	9.6	3.9	0.44	120	1.27	4.48	1.8	13.1	210	4.2
14007		18.35	0.15	2.4	0.016	0.35	31.6	10.9	1.31	161	5.93	4.12	4.3	33.4	380	2.7
14008		13.95	0.12	1.7	0.014	0.41	7.5	8.8	1.08	151	1.10	3.72	3.1	21.1	250	3.1
14009		19.20	0.16	3.2	0.022	0.58	20.6	11.1	1.39	187	1.07	4.22	8.9	30.4	410	3.2
14010		10.40	0.15	1.7	0.006	0.15	7.9	3.4	0.40	128	1.13	4.55	2.2	18.8	250	2.6
14011		12.90	0.14	1.7	0.008	0.22	4.3	7.2	0.94	129	0.70	4.41	2.2	8.8	260	3.2
14012		15.60	0.17	2.5	0.016	0.51	15.2	10.9	1.40	191	1.11	4.10	4.2	28.7	380	3.3
14013		18.35	0.16	2.5	0.017	0.59	26.6	13.3	1.62	226	1.15	3.87	4.7	40.2	400	4.0
14014		16.90	0.15	2.7	0.018	0.40	9.6	14.5	1.79	205	1.29	3.74	4.3	38.5	400	4.0
14015		18.65	0.22	2.1	0.101	0.55	82.1	14.1	1.57	237	2.91	3.35	4.1	52.1	370	3.1
14016		14.85	0.14	2.8	0.015	0.49	8.4	8.3	0.95	159	2.04	3.49	7.1	26.2	280	3.8
14017		16.60	0.14	3.7	0.008	0.87	9.1	11.3	1.35	132	1.65	3.78	4.4	36.1	360	2.8
14018		19.60	0.14	4.4	0.013	0.80	10.0	17.3	2.12	186	1.52	3.49	6.6	49.0	440	2.8
14019		15.25	0.17	2.8	0.018	1.86	33.1	13.5	1.31	240	1.31	3.12	4.2	41.4	360	22.3
14020		14.25	0.15	2.8	0.009	2.66	6.9	8.7	0.74	163	1.05	3.04	4.0	20.2	430	11.2
14021		16.30	0.16	2.0	0.019	4.28	12.8	18.9	1.42	184	0.87	0.74	3.4	34.4	310	10.5
14022		13.55	0.16	2.6	0.006	3.62	11.0	7.4	0.58	165	1.52	2.78	3.4	15.3	410	5.1
14023		15.65	0.21	3.4	0.037	4.32	25.9	9.3	0.58	214	1.77	1.89	5.8	17.2	380	8.5
14024		14.25	0.21	3.1	0.030	4.22	23.0	6.9	0.53	253	1.80	2.20	6.2	16.7	380	7.8
14025		0.26	0.13	<0.1	<0.005	0.01	1.1	1.2	1.09	77	0.10	0.03	0.1	0.7	50	<0.5
14026		15.50	0.15	2.9	0.017	1.16	22.6	12.3	1.22	202	1.59	3.86	4.6	31.2	390	2.9
14027		19.15	0.16	3.0	0.025	1.22	27.8	18.5	1.95	244	1.73	3.25	5.3	49.4	380	6.3
14028		18.50	0.20	3.1	0.016	1.58	68.0	13.5	1.25	182	2.57	3.45	5.0	27.2	360	8.9
14029		16.55	0.22	3.5	0.012	2.44	15.3	8.3	0.74	185	1.11	3.64	5.0	18.9	460	5.1
14030		13.70	0.15	2.3	0.009	2.94	13.3	9.8	0.83	141	1.34	2.62	3.0	16.3	360	5.2
14031		14.45	0.16	2.8	0.007	2.64	9.5	5.3	0.50	129	3.08	3.24	3.4	14.4	420	5.3
14032		15.35	0.22	3.5	0.018	1.88	32.9	10.6	0.99	133	1.66	3.09	4.5	26.6	390	3.9
14033		18.40	0.15	2.6	0.024	2.26	21.6	17.4	1.67	299	1.39	2.24	3.8	72.1	370	5.8
14034		14.95	0.15	2.5	0.012	3.09	12.7	7.7	0.74	152	1.07	2.63	4.0	18.0	340	3.8
14057		13.65	0.23	1.7	0.007	0.59	57.8	5.3	0.51	87	3.28	4.51	2.7	17.5	260	1.9
14035		18.05	0.20	2.6	0.024	1.71	24.9	10.5	0.95	109	1.48	3.69	4.2	41.9	460	7.3
14036		9.09	0.13	1.5	<0.005	0.14	8.7	0.8	0.04	43	1.48	4.75	1.2	5.4	250	3.2
14037		21.3	0.18	3.1	0.037	2.12	27.2	16.5	1.52	173	1.63	3.18	6.7	56.0	570	3.2
14038		12.15	0.15	2.1	0.017	0.81	8.1	6.4	0.60	97	2.77	3.96	3.2	21.6	410	2.2
14039		22.2	0.22	3.3	0.057	2.25	39.0	18.6	1.96	247	1.55	2.64	8.1	59.0	650	6.0

Comments: ***Corrected copy with project name McAra corrected to Iron Mask***

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 9-JUN-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18125489

Sample Description	Method / Analyte / Units / LOD	ME-MS61 Rb ppm 0.1	ME-MS61 Re ppm 0.002	ME-MS61 S % 0.01	ME-MS61 Sb ppm 0.05	ME-MS61 Sc ppm 0.1	ME-MS61 Se ppm 1	ME-MS61 Sn ppm 0.2	ME-MS61 Sr ppm 0.2	ME-MS61 Ta ppm 0.05	ME-MS61 Te ppm 0.05	ME-MS61 Th ppm 0.01	ME-MS61 Ti % 0.005	ME-MS61 Tl ppm 0.02	ME-MS61 U ppm 0.1	ME-MS61 V ppm 1
14001		39.8	<0.002	0.12	0.17	10.7	<1	1.2	119.5	0.53	<0.05	6.88	0.290	0.22	2.2	81
14002		15.7	<0.002	0.06	0.15	9.9	<1	0.7	104.5	0.46	<0.05	6.05	0.258	0.07	2.7	78
14003		12.6	<0.002	0.03	0.14	8.2	<1	0.7	80.9	0.33	<0.05	4.46	0.190	0.07	1.9	62
14004		12.1	<0.002	0.57	0.14	6.8	1	0.7	80.7	0.30	0.05	4.36	0.149	0.08	1.7	52
14005		38.5	<0.002	0.10	0.18	7.6	<1	0.7	93.4	0.34	<0.05	4.57	0.179	0.20	1.5	60
14006		4.7	<0.002	0.37	0.15	4.6	1	0.6	66.4	0.18	<0.05	3.08	0.097	0.03	1.3	31
14007		15.0	<0.002	0.36	0.14	9.1	1	1.0	64.3	0.38	0.05	5.15	0.205	0.10	2.1	70
14008		15.7	<0.002	0.12	0.10	6.6	<1	0.7	68.9	0.32	<0.05	3.81	0.153	0.09	1.1	51
14009		24.5	<0.002	0.14	0.12	9.8	1	1.1	113.5	1.07	<0.05	8.43	0.251	0.11	3.2	73
14010		4.8	<0.002	0.68	0.12	4.5	1	0.5	53.5	0.23	0.05	3.27	0.113	0.03	1.3	30
14011		8.6	<0.002	0.05	0.11	6.7	1	0.6	62.4	0.23	<0.05	3.45	0.145	0.04	1.2	58
14012		21.2	<0.002	0.66	0.14	10.3	1	0.7	87.5	0.39	0.06	6.28	0.222	0.12	1.7	71
14013		27.7	<0.002	0.48	0.22	13.9	1	0.7	71.7	0.38	<0.05	10.45	0.286	0.15	2.3	109
14014		17.0	<0.002	0.36	0.14	13.2	1	0.6	62.0	0.41	<0.05	5.56	0.276	0.09	2.1	84
14015		25.9	<0.002	0.97	0.14	14.2	2	0.9	64.1	0.37	<0.05	5.88	0.280	0.17	1.8	101
14016		16.7	<0.002	0.30	0.13	10.2	1	0.5	55.2	0.95	<0.05	7.41	0.190	0.08	2.9	46
14017		28.4	<0.002	0.16	0.10	10.1	1	1.5	52.0	0.44	<0.05	7.60	0.232	0.14	3.1	65
14018		33.3	<0.002	0.14	0.15	11.9	1	0.8	77.0	0.63	<0.05	11.00	0.306	0.16	4.0	88
14019		73.2	<0.002	0.47	0.18	11.0	1	0.4	50.2	0.36	<0.05	8.07	0.188	0.38	2.2	61
14020		71.9	<0.002	0.20	0.17	6.4	1	0.5	58.7	0.36	<0.05	5.79	0.147	0.28	2.3	42
14021		111.0	<0.002	0.31	0.12	6.2	1	0.7	18.0	0.27	0.07	6.99	0.111	0.50	1.9	36
14022		82.2	<0.002	0.03	0.13	5.8	1	0.6	41.2	0.30	<0.05	5.11	0.129	0.36	1.9	35
14023		129.5	<0.002	0.04	0.14	5.7	1	1.2	73.0	0.49	<0.05	11.85	0.164	0.49	3.8	34
14024		102.0	0.002	0.13	0.14	5.4	1	1.2	65.6	0.52	<0.05	13.30	0.167	0.43	3.6	32
14025		0.3	<0.002	<0.01	0.08	0.2	2	<0.2	78.9	<0.05	<0.05	0.10	0.005	<0.02	0.1	1
14026		60.8	<0.002	0.61	0.15	9.7	1	0.6	61.6	0.42	0.05	6.58	0.237	0.29	2.4	72
14027		64.4	<0.002	0.58	0.13	14.2	1	0.6	53.7	0.47	0.08	9.19	0.275	0.30	2.6	95
14028		60.0	0.002	0.54	0.19	10.3	2	0.9	51.6	0.43	0.13	10.95	0.201	0.33	2.7	60
14029		52.2	<0.002	0.15	0.13	7.4	1	0.8	58.3	0.45	<0.05	9.08	0.175	0.26	3.5	44
14030		63.0	<0.002	0.10	0.12	5.1	1	1.0	37.4	0.27	<0.05	4.54	0.120	0.32	1.8	38
14031		51.1	<0.002	0.14	0.13	6.6	1	0.9	59.9	0.32	<0.05	5.32	0.130	0.25	2.2	53
14032		71.2	<0.002	0.12	0.14	8.2	1	0.6	49.6	0.43	<0.05	7.81	0.187	0.35	2.8	51
14033		84.9	<0.002	2.28	0.36	9.1	4	0.9	55.0	0.35	0.13	6.39	0.151	0.46	2.2	52
14034		72.9	<0.002	0.09	0.15	6.0	1	0.7	72.8	0.34	<0.05	5.99	0.145	0.33	2.1	38
14057		26.9	<0.002	0.06	0.15	4.2	<1	0.4	59.4	0.25	<0.05	4.05	0.123	0.13	1.9	31
14035		83.3	<0.002	0.24	0.16	9.5	1	0.9	72.2	0.39	<0.05	7.35	0.184	0.37	2.1	79
14036		4.0	<0.002	0.35	0.15	4.1	1	0.4	42.2	0.13	<0.05	3.41	0.066	0.02	1.0	34
14037		101.5	0.002	0.21	0.21	13.8	1	1.4	97.8	0.55	0.05	9.15	0.300	0.45	2.9	88
14038		35.2	<0.002	0.11	0.20	6.6	1	0.8	73.7	0.29	<0.05	5.46	0.160	0.16	2.0	45
14039		108.0	<0.002	0.05	0.27	14.4	1	1.7	149.5	0.73	<0.05	11.75	0.351	0.51	4.1	104

Comments: ***Corrected copy with project name McAra corrected to Iron Mask***

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 9-JUN-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18125489

Sample Description	Method / Analyte / Units / LOD	ME-MS61 W ppm 0.1	ME-MS61 Y ppm 0.1	ME-MS61 Zn ppm 2	ME-MS61 Zr ppm 0.5	Ag-OG62 Ag ppm 1	Cu-OG62 Cu % 0.001	Ni-OG62 Ni % 0.001	CRU-QC Pass2mm % 0.01	PUL-QC Pass75um % 0.01
14001		1.9	12.1	13	110.5				72.0	97.0
14002		1.1	11.9	11	103.5					97.8
14003		0.4	14.1	9	80.4					
14004		0.6	8.4	8	70.8					
14005		0.6	10.1	14	73.0					
14006		0.2	7.2	5	44.1					
14007		0.3	7.7	10	85.6					
14008		0.3	6.1	8	58.1					
14009		0.4	13.1	9	107.5					
14010		0.2	6.7	4	58.5					
14011		0.1	7.0	7	60.4					
14012		0.3	13.2	18	86.5					
14013		0.3	10.0	18	91.8					
14014		0.5	12.2	18	95.3					
14015		0.9	9.2	15	76.4					
14016		0.7	13.6	8	100.0					
14017		0.7	10.0	10	138.0					
14018		0.6	11.4	17	165.5					
14019		0.2	10.1	21	104.5					
14020		0.4	7.8	10	103.5					
14021		0.3	7.9	21	76.2					
14022		0.3	6.9	9	100.5					
14023		0.7	11.2	14	128.0					
14024		0.4	10.2	11	119.5					
14025		<0.1	2.0	5	1.4					
14026		0.3	11.8	13	107.5					
14027		0.3	12.5	24	111.0					
14028		0.3	15.6	17	112.5					
14029		0.4	12.5	9	132.0					
14030		0.5	8.5	10	88.5					
14031		0.7	8.1	7	110.5					
14032		0.7	10.8	10	129.5					
14033		0.4	11.5	19	99.5					
14034		0.5	8.2	9	90.5					
14057		0.3	7.7	7	61.6					
14035		1.3	7.5	13	96.8					
14036		0.5	5.5	2	52.9					
14037		1.4	13.3	30	111.0					
14038		0.9	7.6	7	78.3					
14039		1.2	14.8	21	120.0				70.4	97.7

Comments: ***Corrected copy with project name McAra corrected to Iron Mask***

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 9-JUN-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18125489

Sample Description	Method / Analyte / Units / LOD	WEI-21 Recvd Wt. kg 0.02	ME-MS61 Ag ppm 0.01	ME-MS61 Al % 0.01	ME-MS61 As ppm 0.2	ME-MS61 Ba ppm 10	ME-MS61 Be ppm 0.05	ME-MS61 Bi ppm 0.01	ME-MS61 Ca % 0.01	ME-MS61 Cd ppm 0.02	ME-MS61 Ce ppm 0.01	ME-MS61 Co ppm 0.1	ME-MS61 Cr ppm 1	ME-MS61 Cs ppm 0.05	ME-MS61 Cu ppm 0.2	ME-MS61 Fe % 0.01
14040		0.87	0.02	7.85	1.7	570	2.30	0.32	0.46	0.02	77.6	17.3	112	1.76	48.2	4.17
14041		0.07	3.96	5.39	13.5	110	0.51	0.89	3.38	2.11	16.35	967	277	0.75	>10000	17.55
14042		2.29	0.02	7.95	2.1	600	2.57	0.25	0.34	<0.02	79.3	21.9	116	2.09	25.0	4.14
14043		2.05	0.01	7.82	1.5	500	2.04	0.22	0.40	<0.02	80.8	15.9	109	2.32	9.5	4.01
14044		1.66	0.02	5.34	6.9	40	0.99	0.40	0.24	<0.02	15.30	22.9	62	0.13	4.3	1.62
14045		1.84	<0.01	8.13	0.7	510	2.71	0.09	0.35	<0.02	89.5	20.0	112	2.67	1.3	4.83
14046		1.97	0.03	7.77	0.7	250	1.95	0.18	0.27	<0.02	85.7	9.3	99	1.07	1.0	4.47
14047		2.20	0.01	7.53	20.5	160	1.83	0.45	0.26	<0.02	72.0	37.6	95	0.52	1.9	4.16
14048		2.08	0.02	7.64	12.9	190	2.37	0.72	0.26	<0.02	56.9	26.0	90	0.60	6.5	4.01
14049		1.99	0.01	6.89	2.0	10	1.43	0.39	0.20	<0.02	17.65	19.2	81	0.08	1.5	2.48
14050		2.27	<0.01	6.91	2.7	40	1.41	0.24	0.21	<0.02	36.5	16.6	73	0.19	1.4	3.01
14051		2.04	0.02	7.43	28.8	10	1.84	0.83	0.38	<0.02	63.5	58.9	84	<0.05	1.8	5.00
14052		2.22	<0.01	6.66	2.4	30	1.75	0.09	0.22	<0.02	31.2	9.2	67	0.14	1.5	4.36
14053		1.94	0.01	6.87	1.6	40	1.97	0.23	0.21	<0.02	53.5	17.5	95	0.16	1.7	3.74
14054		1.84	<0.01	7.63	1.5	130	1.74	0.13	0.29	<0.02	57.9	11.8	118	0.39	1.0	4.47
14055		1.94	<0.01	7.27	1.2	210	1.97	0.09	0.29	<0.02	49.2	10.3	91	0.78	1.3	3.74
14056		2.11	<0.01	7.77	0.7	330	2.56	0.15	0.70	<0.02	76.8	16.2	100	1.22	0.7	4.15
14058		2.00	<0.01	7.24	1.9	370	2.49	0.25	2.05	<0.02	63.4	39.0	91	1.07	5.0	4.13
14059		2.22	0.01	7.81	2.4	170	1.58	0.12	0.32	<0.02	59.9	17.1	116	0.93	47.5	4.84
14060		2.07	0.02	6.47	1.7	70	1.53	0.21	1.34	<0.02	49.6	21.2	66	0.32	3.3	2.50
14061		2.06	0.02	6.38	10.6	20	1.12	0.17	0.85	<0.02	78.9	29.7	67	0.09	7.0	1.79
14062		1.92	0.01	7.34	5.2	90	1.64	0.22	0.35	<0.02	41.1	13.1	77	0.49	4.3	4.12
14063		1.85	<0.01	7.58	0.8	90	1.72	0.05	0.25	<0.02	84.4	5.4	96	0.80	1.9	4.49
14064		1.52	<0.01	5.99	31.3	30	0.83	0.72	0.47	<0.02	26.8	29.9	62	0.22	3.7	2.38
14065		1.43	0.01	5.85	15.6	30	0.76	0.67	0.94	<0.02	19.60	27.7	51	0.23	5.8	1.94
14066		1.12	<0.01	5.41	27.9	40	0.72	0.70	1.68	<0.02	9.26	39.3	39	0.35	11.3	2.13
14067		1.86	0.01	5.61	14.3	70	0.69	0.63	0.62	<0.02	17.65	30.0	50	0.46	3.7	1.94
14068		1.87	0.01	5.78	7.6	70	0.57	0.29	0.90	<0.02	13.75	15.9	45	0.58	2.3	2.25
14069		1.71	0.01	5.97	4.0	50	0.73	0.19	0.70	<0.02	21.7	11.8	50	0.48	2.1	2.53
14070		1.86	0.01	6.60	7.6	60	1.15	0.25	0.27	<0.02	39.7	16.6	52	0.52	4.0	2.71
14071		1.93	<0.01	8.45	1.6	420	2.76	0.09	0.42	<0.02	50.1	26.6	136	0.91	2.8	5.32
14072		1.82	0.01	6.16	20.4	10	2.76	0.55	0.60	<0.02	63.5	108.5	60	<0.05	3.2	2.72
14073		1.96	0.01	7.21	10.4	50	2.69	0.36	0.55	<0.02	63.6	94.6	90	0.16	2.9	3.61
14074		2.07	<0.01	7.48	10.5	40	1.83	0.22	0.25	<0.02	36.2	17.8	86	0.30	1.2	3.82
14075		1.02	<0.01	0.08	<0.2	10	0.07	0.02	32.8	<0.02	1.03	1.3	2	<0.05	1.5	0.12
14076		2.00	<0.01	5.43	34.7	10	0.58	0.50	1.30	<0.02	22.0	26.4	48	<0.05	3.2	2.50
14077		2.00	<0.01	7.09	11.3	100	1.55	0.42	1.38	<0.02	37.2	13.7	101	0.64	17.3	5.06
14078		1.87	0.03	6.37	11.9	70	2.00	0.82	0.40	<0.02	28.5	23.9	49	0.35	18.9	4.88
14079		0.86	<0.01	6.64	32.6	50	1.17	0.86	0.31	<0.02	42.5	15.9	59	0.27	7.9	3.86
14080		0.85	0.01	6.91	24.3	50	1.26	0.72	0.34	<0.02	42.2	14.0	69	0.27	9.7	3.51

Comments: ***Corrected copy with project name McAra corrected to Iron Mask***

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 9-JUN-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18125489

Sample Description	Method / Analyte / Units / LOD	ME-MS61 Ga ppm 0.05	ME-MS61 Ge ppm 0.05	ME-MS61 Hf ppm 0.1	ME-MS61 In ppm 0.005	ME-MS61 K % 0.01	ME-MS61 La ppm 0.5	ME-MS61 Li ppm 0.2	ME-MS61 Mg % 0.01	ME-MS61 Mn ppm 5	ME-MS61 Mo ppm 0.05	ME-MS61 Na % 0.01	ME-MS61 Nb ppm 0.1	ME-MS61 Ni ppm 0.2	ME-MS61 P ppm 10	ME-MS61 Pb ppm 0.5
14040		21.7	0.22	3.4	0.057	2.22	39.2	18.6	1.94	246	1.32	2.60	8.1	58.7	640	5.7
14041		11.60	0.35	1.3	0.110	0.31	7.4	9.1	3.93	999	5.32	1.16	4.8	>10000	480	13.6
14042		22.6	0.20	3.5	0.042	2.28	38.3	18.7	1.89	238	1.77	2.91	7.5	79.0	630	5.1
14043		20.9	0.21	3.6	0.039	2.03	41.1	17.8	1.87	233	1.32	3.14	7.9	66.0	620	9.5
14044		9.53	0.14	1.6	<0.005	0.29	7.5	3.1	0.27	51	1.79	4.14	1.9	15.4	240	3.8
14045		24.8	0.24	4.3	0.043	2.04	45.5	20.0	2.28	263	1.62	3.05	12.8	56.6	630	4.3
14046		23.7	0.22	4.3	0.030	1.08	42.8	16.5	2.08	198	1.63	3.39	10.3	46.8	580	2.9
14047		21.4	0.20	4.1	0.029	0.68	35.7	13.5	1.73	166	1.72	3.94	9.1	41.1	560	7.4
14048		21.7	0.21	4.4	0.033	0.84	27.5	13.7	1.60	160	2.08	3.90	8.8	40.2	530	4.1
14049		16.95	0.15	5.0	0.005	0.09	8.6	7.5	0.95	117	1.53	4.99	8.4	25.5	510	2.2
14050		18.70	0.18	4.1	0.009	0.24	16.9	9.3	1.18	134	1.57	4.54	7.5	30.1	450	2.6
14051		12.95	0.19	4.0	<0.005	0.08	30.4	0.9	0.07	39	1.63	6.06	1.6	20.5	450	2.6
14052		13.65	0.17	3.1	0.007	0.16	14.5	7.0	0.86	114	1.37	4.56	4.5	20.3	390	2.0
14053		15.75	0.19	3.6	0.009	0.20	25.7	11.3	1.36	162	1.30	4.32	5.2	38.6	500	1.8
14054		19.65	0.20	3.5	0.018	0.51	29.1	18.4	2.20	237	1.37	3.82	6.5	59.3	610	6.5
14055		18.60	0.20	3.0	0.030	1.01	24.1	15.8	1.76	183	0.92	3.37	5.5	43.2	490	3.6
14056		21.8	0.20	4.1	0.040	1.35	39.7	19.1	1.87	259	1.27	3.40	10.8	48.3	610	5.3
14058		20.7	0.21	3.9	0.039	1.36	32.6	15.7	1.64	365	1.26	3.16	9.7	43.9	530	5.0
14059		21.8	0.21	3.8	0.023	0.86	29.6	19.5	2.42	260	1.49	3.72	7.6	55.8	600	2.2
14060		14.95	0.23	3.2	0.009	0.43	24.7	10.5	1.10	206	0.79	4.07	5.8	29.7	370	2.4
14061		12.05	0.20	2.4	0.008	0.17	43.7	6.1	0.70	121	1.03	4.60	4.6	18.0	350	2.8
14062		20.7	0.19	2.8	0.018	0.57	19.7	15.5	1.76	186	1.14	4.03	5.6	41.6	480	1.8
14063		23.4	0.22	3.0	0.020	0.61	41.9	17.9	2.11	233	1.50	3.95	6.0	50.4	520	1.5
14064		13.40	0.16	2.3	0.007	0.26	12.8	8.0	0.84	133	0.73	4.21	3.8	28.4	300	3.1
14065		12.15	0.14	1.7	0.009	0.25	9.9	6.8	0.72	146	0.78	4.19	2.9	21.1	250	2.2
14066		11.25	0.15	1.4	0.009	0.38	4.8	7.2	0.69	176	0.86	3.71	2.2	24.3	180	2.6
14067		11.55	0.16	1.4	0.007	0.60	8.9	7.5	0.66	116	0.87	3.92	2.7	21.1	230	2.1
14068		11.65	0.15	1.6	0.008	0.68	7.0	6.7	0.54	131	0.98	4.04	2.3	15.2	210	2.1
14069		12.50	0.17	1.8	0.008	0.45	10.4	7.0	0.65	145	0.66	4.22	3.1	17.3	270	1.5
14070		15.40	0.17	1.9	0.007	0.47	18.4	10.3	1.04	137	0.63	4.34	3.0	28.9	280	1.7
14071		24.3	0.18	3.4	0.044	1.82	23.6	20.8	2.45	273	1.33	2.88	7.7	71.2	660	1.5
14072		13.20	0.20	2.2	0.005	0.10	32.5	3.6	0.42	80	0.89	4.65	2.2	29.3	300	2.1
14073		19.10	0.21	3.0	0.009	0.29	30.8	9.0	1.06	134	1.44	4.74	4.4	38.7	440	1.9
14074		20.3	0.16	2.8	0.013	0.33	16.5	14.4	1.66	180	1.29	4.63	4.5	41.6	460	1.5
14075		0.45	0.13	<0.1	<0.005	0.01	1.2	1.7	1.74	87	0.12	0.04	0.1	0.9	60	0.6
14076		10.65	0.15	1.5	0.005	0.12	10.4	3.4	0.40	138	1.10	4.11	1.8	18.4	210	3.1
14077		19.40	0.17	2.3	0.031	0.66	18.5	21.0	2.56	309	1.67	3.36	4.7	47.8	420	2.3
14078		14.85	0.17	1.5	0.011	0.41	13.6	8.3	0.82	114	1.04	4.09	2.0	25.2	260	1.6
14079		15.45	0.21	1.9	0.014	0.32	19.6	9.7	1.11	132	0.91	4.28	3.2	27.6	330	1.2
14080		16.55	0.19	2.2	0.016	0.34	20.0	10.2	1.13	138	1.22	4.55	3.8	25.0	380	1.3

Comments: ***Corrected copy with project name McAra corrected to Iron Mask***

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 9-JUN-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18125489

Sample Description	Method / Analyte / Units / LOD	ME-MS61 Rb ppm 0.1	ME-MS61 Re ppm 0.002	ME-MS61 S % 0.01	ME-MS61 Sb ppm 0.05	ME-MS61 Sc ppm 0.1	ME-MS61 Se ppm 1	ME-MS61 Sn ppm 0.2	ME-MS61 Sr ppm 0.2	ME-MS61 Ta ppm 0.05	ME-MS61 Te ppm 0.05	ME-MS61 Th ppm 0.01	ME-MS61 Ti % 0.005	ME-MS61 Tl ppm 0.02	ME-MS61 U ppm 0.1	ME-MS61 V ppm 1
14040		107.0	<0.002	0.06	0.27	14.2	1	1.7	148.5	0.71	0.05	11.75	0.346	0.54	4.2	101
14041		10.6	0.041	8.52	3.52	8.8	23	2.4	174.0	0.31	4.26	1.11	0.524	0.18	0.3	78
14042		106.5	<0.002	0.14	0.26	14.4	1	1.7	108.0	0.67	0.08	11.30	0.333	0.48	3.3	103
14043		102.0	<0.002	0.07	0.26	14.6	1	1.8	148.5	0.71	<0.05	11.10	0.337	0.49	3.9	97
14044		9.2	<0.002	0.33	0.23	4.4	1	0.5	57.1	0.18	0.14	3.94	0.093	0.04	1.5	32
14045		96.7	<0.002	0.01	0.28	16.7	1	3.0	119.0	1.30	<0.05	18.85	0.398	0.48	6.3	115
14046		55.2	<0.002	0.07	0.21	14.4	1	2.7	110.5	1.09	0.06	15.15	0.353	0.22	4.9	99
14047		32.6	<0.002	0.53	0.20	12.7	1	1.8	92.7	0.94	0.05	13.50	0.329	0.10	5.7	90
14048		40.1	<0.002	0.43	0.26	13.4	1	2.5	97.0	1.04	0.05	12.50	0.313	0.14	4.1	92
14049		3.0	<0.002	0.26	0.20	8.6	1	1.0	73.5	0.96	0.06	11.15	0.288	0.03	3.4	60
14050		10.3	<0.002	0.22	0.19	9.9	1	1.2	86.1	0.85	<0.05	9.86	0.255	0.06	3.0	66
14051		1.9	<0.002	0.77	0.20	4.2	1	0.8	56.3	0.25	0.05	9.34	0.082	<0.02	2.5	92
14052		6.8	<0.002	0.06	0.16	7.6	1	1.0	68.8	0.50	<0.05	7.81	0.200	0.04	2.2	71
14053		9.1	<0.002	0.17	0.19	11.6	1	0.9	59.1	0.52	<0.05	6.59	0.285	0.05	2.4	82
14054		24.4	<0.002	0.04	0.20	14.6	<1	1.1	81.3	0.59	<0.05	8.01	0.358	0.09	2.9	107
14055		50.8	<0.002	0.05	0.18	11.2	1	1.3	92.1	0.53	<0.05	6.81	0.283	0.21	2.4	82
14056		82.6	<0.002	0.03	0.27	14.6	1	2.3	126.0	1.13	0.05	14.70	0.376	0.34	5.1	105
14058		79.1	<0.002	0.39	0.22	13.2	1	2.0	140.0	1.01	<0.05	12.80	0.337	0.36	4.5	94
14059		48.5	<0.002	0.08	0.17	15.6	<1	1.6	82.0	0.71	<0.05	9.16	0.363	0.23	2.9	112
14060		21.0	<0.002	0.17	0.13	8.8	1	1.0	92.2	0.54	<0.05	11.40	0.224	0.11	2.7	57
14061		6.6	<0.002	0.17	0.14	7.2	1	0.8	62.0	0.41	<0.05	7.22	0.204	0.03	2.8	43
14062		29.5	<0.002	0.15	0.15	12.8	1	0.8	80.6	0.50	<0.05	9.92	0.273	0.16	2.4	95
14063		33.1	<0.002	0.01	0.14	13.3	1	1.0	66.1	0.55	<0.05	6.98	0.297	0.17	2.0	97
14064		11.9	<0.002	0.59	0.13	6.1	1	0.5	47.2	0.39	0.07	5.38	0.176	0.07	2.2	47
14065		11.2	<0.002	0.41	0.12	5.2	1	0.5	44.0	0.30	0.05	3.70	0.141	0.07	1.6	40
14066		16.1	<0.002	0.72	0.12	4.9	2	0.5	55.5	0.24	0.05	3.51	0.107	0.11	1.1	41
14067		19.8	<0.002	0.52	0.13	4.9	1	0.5	48.2	0.29	0.07	3.50	0.126	0.12	1.3	38
14068		22.5	<0.002	0.23	0.12	5.2	1	0.9	54.4	0.23	0.06	3.58	0.111	0.14	1.5	49
14069		21.1	<0.002	0.13	0.12	6.0	1	0.9	49.3	0.29	<0.05	3.62	0.145	0.13	1.4	54
14070		25.7	<0.002	0.22	0.17	7.5	1	0.7	56.7	0.30	0.05	4.12	0.158	0.14	1.5	59
14071		93.0	<0.002	0.05	0.16	17.3	1	1.8	100.5	0.67	<0.05	9.15	0.410	0.40	2.8	132
14072		2.8	<0.002	1.07	0.12	5.7	1	0.7	49.7	0.26	0.06	4.17	0.124	0.02	1.4	42
14073		10.8	<0.002	0.86	0.12	10.5	1	1.2	60.6	0.43	0.05	6.42	0.228	0.05	2.0	71
14074		13.4	<0.002	0.17	0.13	10.8	1	0.7	50.3	0.44	<0.05	6.40	0.248	0.07	2.1	79
14075		0.2	<0.002	<0.01	0.11	0.4	2	<0.2	78.1	<0.05	<0.05	0.09	0.006	<0.02	0.1	3
14076		3.2	<0.002	0.56	0.13	5.6	1	0.4	37.6	0.20	<0.05	3.70	0.104	0.02	1.3	41
14077		29.1	<0.002	0.24	0.16	16.2	1	0.8	79.9	0.46	<0.05	5.47	0.322	0.15	1.4	112
14078		15.8	<0.002	0.41	0.13	8.8	1	0.8	43.7	0.27	<0.05	3.50	0.125	0.07	1.3	79
14079		12.8	<0.002	0.58	0.10	8.3	1	0.5	44.3	0.30	<0.05	3.93	0.168	0.07	1.6	74
14080		13.8	<0.002	0.48	0.11	8.7	2	0.5	48.0	0.37	0.06	5.25	0.199	0.07	1.9	67

Comments: ***Corrected copy with project name McAra corrected to Iron Mask***

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 9-JUN-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18125489

Sample Description	Method / Analyte / Units / LOD	ME-MS61 W ppm 0.1	ME-MS61 Y ppm 0.1	ME-MS61 Zn ppm 2	ME-MS61 Zr ppm 0.5	Ag-OG62 Ag ppm 1	Cu-OG62 Cu % 0.001	Ni-OG62 Ni % 0.001	CRU-QC Pass2mm % 0.01	PUL-QC Pass75um % 0.01
14040		1.2	14.5	22	120.5					91.0
14041		2.1	9.1	142	50.8		1.600	4.65		
14042		1.3	12.6	19	123.5					91.5
14043		1.0	13.9	22	128.0					
14044		0.3	5.0	4	55.0					
14045		1.2	20.2	19	149.0					
14046		1.1	17.3	14	154.5					
14047		2.7	13.8	12	147.5					
14048		1.2	15.9	13	152.0					
14049		0.7	8.6	7	173.0					
14050		0.7	7.9	9	145.0					
14051		0.7	12.1	2	138.5					
14052		2.4	8.8	7	111.5					
14053		0.5	14.7	10	122.0					
14054		0.8	13.9	15	124.0					
14055		0.9	13.2	13	107.5					
14056		0.8	18.3	16	140.5					
14058		0.7	16.5	15	135.0					
14059		0.6	10.7	22	130.0					
14060		0.7	16.5	11	110.0					
14061		0.4	17.4	7	87.0					
14062		0.5	9.9	16	102.5					
14063		0.5	12.4	19	110.0					
14064		0.2	6.2	8	81.1					
14065		0.2	4.1	7	59.0					
14066		0.1	3.3	7	48.1					
14067		0.2	3.8	7	52.1					
14068		0.2	4.0	6	53.9					
14069		0.2	4.7	8	63.6					
14070		0.2	6.2	9	68.5					
14071		1.3	14.2	23	120.0					
14072		0.3	21.2	3	79.1					
14073		0.5	19.9	7	106.0					
14074		0.2	8.4	10	99.7					
14075		<0.1	2.0	4	1.7					
14076		0.1	6.1	4	51.8					
14077		0.3	12.7	16	78.5					
14078		0.2	8.6	6	53.3					
14079		0.3	7.6	7	68.5					
14080		0.3	7.6	7	82.7				69.9	93.0

Comments: ***Corrected copy with project name McAra corrected to Iron Mask***

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 9-JUN-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18125489

Sample Description	Method / Analyte / Units / LOD	WEI-21 Recvd Wt. kg 0.02	ME-MS61 Ag ppm 0.01	ME-MS61 Al % 0.01	ME-MS61 As ppm 0.2	ME-MS61 Ba ppm 10	ME-MS61 Be ppm 0.05	ME-MS61 Bi ppm 0.01	ME-MS61 Ca % 0.01	ME-MS61 Cd ppm 0.02	ME-MS61 Ce ppm 0.01	ME-MS61 Co ppm 0.1	ME-MS61 Cr ppm 1	ME-MS61 Cs ppm 0.05	ME-MS61 Cu ppm 0.2	ME-MS61 Fe % 0.01
14081		0.06	>100	4.38	686	540	0.82	58.6	0.61	26.5	32.4	10.1	33	2.75	5050	2.14
14082		2.03	0.20	5.73	16.3	40	1.06	0.43	0.52	0.03	44.2	14.0	40	0.16	10.3	1.63

Comments: ***Corrected copy with project name McAra corrected to Iron Mask***

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 9-JUN-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18125489

Sample Description	Method	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61
	Analyte	Ga	Ge	Hf	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni	P	Pb
	Units	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm
	LOD	0.05	0.05	0.1	0.005	0.01	0.5	0.2	0.01	5	0.05	0.01	0.1	0.2	10	0.5
14081		21.5	0.24	2.7	5.42	0.66	15.8	20.1	0.18	228	4.61	0.44	7.8	59.8	570	1030
14082		12.00	0.20	1.5	0.015	0.35	21.1	5.5	0.53	93	0.79	4.23	1.8	14.7	200	3.1

Comments: ***Corrected copy with project name McAra corrected to Iron Mask***

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 9-JUN-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18125489

Sample Description	Method / Analyte / Units / LOD	ME-MS61 Rb ppm 0.1	ME-MS61 Re ppm 0.002	ME-MS61 S % 0.01	ME-MS61 Sb ppm 0.05	ME-MS61 Sc ppm 0.1	ME-MS61 Se ppm 1	ME-MS61 Sn ppm 0.2	ME-MS61 Sr ppm 0.2	ME-MS61 Ta ppm 0.05	ME-MS61 Te ppm 0.05	ME-MS61 Th ppm 0.01	ME-MS61 Ti % 0.005	ME-MS61 Tl ppm 0.02	ME-MS61 U ppm 0.1	ME-MS61 V ppm 1
14081		27.6	<0.002	2.14	86.4	4.2	35	5.8	444	0.59	41.0	6.51	0.216	1.75	2.4	33
14082		9.0	<0.002	0.24	0.23	4.2	1	0.3	34.7	0.20	0.10	3.19	0.092	0.05	0.9	34

Comments: ***Corrected copy with project name McAra corrected to Iron Mask***

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 9-JUN-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18125489

Sample Description	Method Analyte Units LOD	ME-MS61 W ppm 0.1	ME-MS61 Y ppm 0.1	ME-MS61 Zn ppm 2	ME-MS61 Zr ppm 0.5	Ag-OG62 Ag ppm 1	Cu-OG62 Cu % 0.001	Ni-OG62 Ni % 0.001	CRU-QC Pass2mm % 0.01	PUL-QC Pass75um % 0.01
14081		13.1	6.5	4120	89.8	116				
14082		0.1	5.8	9	49.9					

Comments: ***Corrected copy with project name McAra corrected to Iron Mask***

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 9-JUN-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18125489

CERTIFICATE COMMENTS

ANALYTICAL COMMENTS

REE's may not be totally soluble in this method.

Applies to Method: ME-MS61

LABORATORY ADDRESSES

Processed at ALS Sudbury located at 1351-B Kelly Lake Road, Unit #1, Sudbury, ON, Canada.

Applies to Method:

CRU-31	CRU-QC	LOG-22	LOG-24
PUL-31	PUL-QC	SPL-21	WEI-21

Processed at ALS Vancouver located at 2103 Dollarton Hwy, North Vancouver, BC, Canada.

Applies to Method:

Ag-OG62	Cu-OG62	ME-MS61	ME-OG62
Ni-OG62			