ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 7-MAY-2018
This copy reported on
8-MAY-2018
Account: BMRPLLBW

CERTIFICATE SD18098245

Project: Iron Mask

This report is for 206 Drill Core samples submitted to our lab in Sudbury, ON, Canada on 30-APR-2018.

The following have access to data associated with this certificate:

SANDY DE LA MARE	PETER DOYLE	JON EDWARDS
MIKE HENDRICKSON	FRANK PLOEGER	IAN PRINGLE
MERCEDES RICH	CLYDE SMITH	

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
LOG-24	Pulp Login - Rcd w/o Barcode
CRU-31	Fine crushing - 70% <2mm
CRU-QC	Crushing QC Test
PUL-QC	Pulverizing QC Test
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
ME-OG62	Ore Grade Elements - Four Acid	ICP-AES
Cu-OG62	Ore Grade Cu - Four Acid	ICP-AES
Ni-OG62	Ore Grade Ni - Four Acid	ICP-AES
ME-MS61	48 element four acid ICP-MS	
Ag-OG62	Ore Grade Ag - Four Acid	ICP-AES

To: **BATTERY MINERAL RESOURCES LTD.**
ATTN: PETER DOYLE
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

***** See Appendix Page for comments regarding this certificate *****

Signature:
Colin Ramshaw, Vancouver Laboratory Manager

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 7-MAY-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18098245

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	ME-MS61 Ag ppm 0.01	ME-MS61 Al % 0.01	ME-MS61 As ppm 0.2	ME-MS61 Ba ppm 10	ME-MS61 Be ppm 0.05	ME-MS61 Bi ppm 0.01	ME-MS61 Ca % 0.01	ME-MS61 Cd ppm 0.02	ME-MS61 Ce ppm 0.01	ME-MS61 Co ppm 0.1	ME-MS61 Cr ppm 1	ME-MS61 Cs ppm 0.05	ME-MS61 Cu ppm 0.2	ME-MS61 Fe % 0.01
7503		0.87	0.16	5.34	8.8	60	0.94	1.11	1.41	0.02	53.9	138.0	64	0.15	22.3	4.04
7504		1.54	0.07	1.63	5.5	10	0.41	0.85	0.71	<0.02	15.80	78.0	49	<0.05	4.0	6.49
7505		1.90	0.04	3.53	4.0	140	3.40	0.36	6.52	<0.02	25.0	49.1	39	1.83	142.5	26.3
7506		2.67	0.13	4.96	4.9	160	2.88	0.56	6.13	<0.02	70.1	46.6	67	1.88	124.5	19.75
7507		2.91	0.33	3.11	12.4	80	4.54	0.70	5.22	<0.02	322	88.9	41	0.46	567	32.2
7508		2.82	0.05	3.90	3.9	110	1.90	0.39	7.06	0.02	183.0	39.6	51	0.96	98.9	21.5
7509		2.39	0.04	4.64	7.0	30	1.47	0.47	11.05	0.02	76.5	20.2	49	<0.05	49.2	12.65
7510		2.61	0.04	4.52	10.9	40	1.50	0.60	13.00	0.02	61.1	28.0	40	0.06	100.5	15.50
7511		1.16	0.02	5.11	4.8	160	1.85	0.52	9.66	0.02	124.0	42.4	49	2.33	43.2	15.50
7512		1.81	0.04	5.41	9.3	280	1.54	0.62	3.43	<0.02	235	138.0	54	3.90	14.2	17.50
7513		2.00	0.01	0.60	1.6	20	0.32	0.03	0.20	<0.02	25.9	10.0	47	0.20	1.7	1.96
7514		2.00	0.04	3.54	6.5	30	0.70	0.21	0.15	<0.02	80.0	46.6	47	0.09	6.3	1.52
7515		1.49	0.04	4.87	5.2	70	1.20	0.22	0.29	<0.02	143.5	46.9	38	0.17	6.2	1.77
7516		2.40	0.01	5.03	3.8	240	1.82	0.09	0.20	<0.02	343	57.8	58	1.93	11.3	25.2
7517		1.90	0.06	4.70	23.4	90	1.25	0.83	0.41	<0.02	220	106.0	70	0.26	8.2	4.53
7518		1.31	0.05	5.11	8.0	40	1.07	0.33	0.23	<0.02	88.2	34.2	39	0.05	10.2	1.74
7519		2.31	0.03	5.76	9.8	50	1.42	0.34	0.42	0.02	115.5	42.9	25	0.06	9.3	1.89
7520		1.92	0.06	3.88	11.9	80	2.87	0.21	0.41	0.04	161.5	33.7	34	0.24	22.6	1.57
7521		1.57	0.04	7.96	4.2	240	3.35	0.07	1.20	<0.02	52.5	60.6	109	1.04	18.9	6.74
7522		1.26	0.01	7.22	5.7	210	1.47	0.07	1.02	<0.02	164.5	46.2	94	1.22	14.9	6.83
7523		1.77	0.01	7.26	5.7	200	1.14	0.10	1.18	<0.02	217	30.2	88	0.98	16.7	7.07
7524		2.12	0.02	7.75	3.1	340	1.90	0.09	1.35	<0.02	114.5	56.7	97	2.28	9.6	12.30
7525		0.84	<0.01	0.08	<0.2	10	0.06	0.01	33.1	<0.02	1.29	1.6	3	<0.05	2.7	0.14
7526		1.25	0.02	7.43	2.2	390	2.80	0.15	3.60	<0.02	30.1	38.6	78	3.42	19.4	9.07
7527		1.46	0.05	7.41	3.0	130	1.08	0.30	6.23	0.03	19.65	43.1	56	0.95	100.0	7.50
7528		1.90	0.02	7.58	3.5	120	1.08	0.26	5.71	<0.02	23.5	45.2	53	1.01	95.7	7.95
7529		2.43	0.02	7.27	1.9	100	1.26	0.24	4.58	<0.02	18.30	42.8	57	0.81	80.3	7.96
7530		2.09	0.03	7.48	2.4	110	1.40	0.29	5.56	<0.02	19.10	45.2	54	0.76	94.2	8.39
7531		2.05	0.03	1.87	2.4	20	0.72	0.09	0.21	0.02	3.01	22.6	37	0.06	4.7	3.37
7532		2.12	0.01	0.74	0.8	10	0.41	0.03	0.05	<0.02	6.51	6.1	28	<0.05	2.1	0.79
7533		2.12	0.01	2.87	1.2	10	0.86	0.08	0.18	<0.02	4.57	23.5	47	0.06	1.6	3.17
7534		1.95	0.01	0.33	2.1	10	0.31	0.13	0.03	<0.02	2.06	16.8	38	<0.05	1.6	0.66
7535		2.26	0.01	0.19	0.5	10	0.30	0.01	0.02	<0.02	0.17	1.5	41	<0.05	1.1	0.32
7536		2.19	0.01	0.35	3.4	10	0.32	0.21	0.02	<0.02	0.18	17.4	39	0.05	1.9	1.20
7537		2.52	0.01	1.38	1.3	20	0.55	0.07	0.15	<0.02	2.01	23.5	30	0.10	2.5	3.30
7538		2.21	0.01	3.47	1.5	20	1.00	0.13	0.32	<0.02	5.09	47.2	41	0.13	3.9	5.22
7539		0.42	0.06	3.87	5.5	30	0.99	0.56	0.26	<0.02	3.38	175.0	49	0.27	8.6	8.11
7540		0.50	0.03	3.43	5.5	30	0.87	0.54	0.24	<0.02	3.11	188.0	38	0.23	8.0	7.49
7541		0.08	3.91	5.51	14.3	120	0.52	0.88	3.46	2.28	16.35	990	269	0.73	>10000	18.05
7542		0.91	0.02	0.31	1.0	10	0.41	0.14	0.10	<0.02	0.54	34.9	23	0.05	8.5	2.94

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 7-MAY-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18098245

Sample Description	Method / Analyte / Units / LOR	ME-MS61 Ga ppm 0.05	ME-MS61 Ge ppm 0.05	ME-MS61 Hf ppm 0.1	ME-MS61 In ppm 0.005	ME-MS61 K % 0.01	ME-MS61 La ppm 0.5	ME-MS61 Li ppm 0.2	ME-MS61 Mg % 0.01	ME-MS61 Mn ppm 5	ME-MS61 Mo ppm 0.05	ME-MS61 Na % 0.01	ME-MS61 Nb ppm 0.1	ME-MS61 Ni ppm 0.2	ME-MS61 P ppm 10	ME-MS61 Pb ppm 0.5
7503		13.45	0.07	2.4	0.020	0.22	28.0	6.5	0.41	190	7.35	3.81	3.6	15.8	340	3.5
7504		4.54	<0.05	0.6	0.007	0.07	7.9	1.0	0.06	100	28.6	1.26	1.2	8.7	120	2.0
7505		18.25	0.15	2.2	0.534	1.20	11.9	16.6	2.41	1170	0.58	0.87	5.5	31.0	210	3.1
7506		15.65	0.15	3.6	0.684	1.24	43.7	17.7	2.31	1270	3.26	1.26	7.3	29.0	370	6.1
7507		15.55	0.62	2.4	0.690	0.40	228	10.2	2.01	1220	0.32	0.94	4.6	57.2	250	6.3
7508		17.00	0.22	2.5	0.600	0.63	122.0	13.2	2.02	1630	0.23	0.75	5.5	46.1	190	6.9
7509		15.15	0.11	2.6	0.395	0.09	43.8	2.5	1.58	2390	0.32	0.79	8.4	34.2	320	10.8
7510		14.85	0.11	2.6	0.357	0.08	28.9	2.8	1.55	2720	0.14	0.31	8.0	39.2	290	11.1
7511		22.7	0.15	3.2	0.189	1.48	71.0	20.5	3.18	2230	0.14	1.24	9.2	53.6	320	7.8
7512		53.8	0.34	3.5	0.173	2.91	134.0	49.0	5.13	1660	1.41	0.44	10.1	124.0	390	5.5
7513		4.75	<0.05	0.3	0.035	0.15	13.6	3.8	0.36	139	3.44	0.14	0.9	10.2	40	4.4
7514		10.70	0.07	2.5	0.009	0.13	43.4	3.3	0.35	104	13.70	2.57	5.0	13.1	200	6.8
7515		14.00	0.10	3.8	0.020	0.30	80.6	3.6	0.29	96	14.65	3.76	8.3	11.6	360	8.3
7516		50.2	0.51	5.7	0.077	1.71	221	37.5	3.45	816	0.70	1.73	11.2	75.2	460	5.1
7517		14.00	0.18	2.8	0.021	0.34	113.5	5.2	0.40	125	8.42	3.23	6.1	19.3	400	16.6
7518		13.20	0.07	4.0	0.009	0.14	40.9	1.5	0.09	60	4.67	4.28	12.8	5.5	270	7.5
7519		14.80	0.10	4.9	0.011	0.16	59.2	2.3	0.16	70	5.00	4.63	20.5	6.8	330	8.9
7520		12.40	0.13	3.0	0.015	0.28	73.4	5.5	0.39	118	4.52	2.58	12.9	21.5	430	68.7
7521		39.0	0.09	4.7	0.022	1.12	22.7	32.2	3.33	672	12.30	4.23	11.5	106.0	1240	21.9
7522		30.5	0.15	3.9	0.029	1.13	91.5	23.6	2.81	595	3.17	3.52	8.9	81.1	970	4.7
7523		27.9	0.20	3.8	0.051	1.06	118.5	21.8	2.51	558	0.75	3.61	9.0	41.5	980	8.7
7524		29.5	0.15	4.2	0.041	2.00	64.6	25.0	3.22	735	0.16	3.65	8.3	65.7	990	11.5
7525		0.28	<0.05	<0.1	<0.005	0.02	1.3	1.2	1.09	80	0.14	0.03	0.1	<0.2	60	<0.5
7526		20.7	0.11	2.8	0.092	2.41	13.6	22.0	3.82	1000	0.20	2.99	6.2	76.4	690	3.7
7527		16.75	0.07	1.5	0.070	0.73	9.2	14.6	3.48	1080	0.65	2.56	3.0	84.5	330	4.5
7528		18.80	0.07	1.6	0.072	0.75	11.5	17.6	3.69	999	0.42	2.60	3.1	87.7	350	3.7
7529		18.65	0.07	1.5	0.062	0.61	9.1	16.2	3.35	852	0.59	2.74	3.0	81.3	330	2.9
7530		19.00	0.08	1.5	0.081	0.61	9.2	16.6	3.64	949	0.49	2.54	3.0	81.4	340	3.3
7531		7.97	<0.05	0.5	0.006	0.06	1.5	3.5	0.48	102	3.81	1.07	0.9	20.0	90	8.1
7532		2.29	<0.05	0.4	<0.005	0.03	3.4	1.0	0.07	40	2.18	0.52	1.1	3.8	50	2.4
7533		12.25	<0.05	0.7	0.006	0.05	2.5	4.8	0.67	114	4.01	1.76	1.3	26.9	140	2.1
7534		1.57	<0.05	<0.1	<0.005	0.03	1.2	1.2	0.11	45	2.64	0.15	0.2	5.7	20	2.2
7535		0.70	<0.05	<0.1	<0.005	0.03	<0.5	1.0	0.05	32	2.48	0.08	<0.1	2.5	<10	1.9
7536		3.26	<0.05	<0.1	<0.005	0.03	<0.5	1.7	0.25	62	2.58	0.06	0.1	11.6	10	2.7
7537		8.86	<0.05	0.3	0.009	0.08	1.2	4.6	0.62	107	3.95	0.60	0.6	23.5	60	2.2
7538		15.50	<0.05	0.8	0.018	0.09	3.0	7.0	1.06	160	8.18	1.94	1.5	33.7	200	2.4
7539		21.3	0.06	0.9	0.028	0.19	1.8	10.1	1.55	172	20.5	1.86	1.6	57.1	180	4.3
7540		19.55	0.06	0.8	0.022	0.17	1.7	9.5	1.46	170	20.6	1.57	1.4	54.6	160	3.1
7541		12.40	0.33	1.3	0.120	0.31	6.8	10.1	4.02	1010	5.22	1.19	4.9	>10000	490	13.8
7542		2.60	0.05	0.1	<0.005	0.04	<0.5	1.7	0.18	49	16.20	0.11	0.1	19.0	10	2.0

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 7-MAY-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18098245

Sample Description	Method / Analyte / Units / LOR	ME-MS61 Rb ppm 0.1	ME-MS61 Re ppm 0.002	ME-MS61 S % 0.01	ME-MS61 Sb ppm 0.05	ME-MS61 Sc ppm 0.1	ME-MS61 Se ppm 1	ME-MS61 Sn ppm 0.2	ME-MS61 Sr ppm 0.2	ME-MS61 Ta ppm 0.05	ME-MS61 Te ppm 0.05	ME-MS61 Th ppm 0.01	ME-MS61 Ti % 0.005	ME-MS61 Tl ppm 0.02	ME-MS61 U ppm 0.1	ME-MS61 V ppm 1
7503		8.4	<0.002	0.72	0.24	6.0	2	1.9	36.5	0.35	0.09	5.95	0.150	0.05	2.0	59
7504		1.7	0.003	0.40	0.16	2.6	1	3.1	9.0	0.07	0.07	1.42	0.028	0.02	0.9	91
7505		66.7	<0.002	0.30	0.40	6.4	1	4.8	107.5	0.43	<0.05	5.86	0.144	0.45	2.4	43
7506		68.0	<0.002	0.18	0.62	10.5	1	5.2	179.5	0.65	<0.05	11.40	0.215	0.41	7.2	59
7507		17.0	0.003	0.63	0.63	6.0	1	4.4	91.7	0.35	0.10	17.80	0.150	0.12	6.5	41
7508		35.2	<0.002	0.20	0.70	7.5	1	4.3	138.5	0.44	<0.05	7.35	0.163	0.22	5.6	49
7509		1.9	<0.002	0.02	1.25	8.2	1	3.1	181.5	0.53	<0.05	11.20	0.179	<0.02	3.1	48
7510		2.3	<0.002	0.12	0.95	7.1	1	2.9	212	0.53	<0.05	8.63	0.165	<0.02	4.4	46
7511		86.6	<0.002	0.42	0.45	10.3	1	3.1	179.0	0.61	<0.05	9.71	0.190	0.53	3.8	65
7512		161.0	<0.002	1.17	0.25	14.0	1	2.9	59.1	0.66	0.06	11.00	0.196	1.08	6.7	122
7513		6.6	<0.002	0.06	0.22	1.5	<1	0.6	9.4	0.06	<0.05	1.22	0.018	0.05	1.5	19
7514		3.6	<0.002	0.37	0.24	2.2	1	0.7	11.1	0.39	<0.05	25.0	0.098	0.03	10.5	17
7515		9.2	0.002	0.33	0.22	3.0	1	1.7	31.2	0.53	<0.05	39.3	0.119	0.07	15.0	24
7516		37.8	<0.002	0.26	0.27	8.7	<1	7.8	25.9	1.40	<0.05	30.8	0.239	0.62	20.1	96
7517		13.0	<0.002	0.91	0.43	5.4	1	2.6	60.6	0.44	0.09	22.5	0.173	0.09	27.7	66
7518		2.6	<0.002	0.31	0.20	2.6	1	1.9	25.9	1.31	<0.05	31.8	0.124	0.03	11.7	22
7519		3.7	<0.002	0.36	0.23	3.5	1	1.7	45.5	2.12	<0.05	54.3	0.156	0.03	18.8	23
7520		11.8	<0.002	0.24	0.38	6.3	1	1.1	65.8	0.87	<0.05	32.9	0.157	0.08	163.0	46
7521		32.9	<0.002	0.06	0.37	40.4	1	3.6	54.2	0.60	<0.05	4.07	1.190	0.36	87.5	355
7522		51.3	<0.002	0.07	0.32	31.5	1	4.5	34.4	0.49	<0.05	2.98	0.996	0.35	9.8	256
7523		44.6	<0.002	0.04	0.44	32.5	<1	5.4	46.0	0.48	<0.05	3.05	0.974	0.30	17.1	257
7524		99.7	<0.002	0.03	0.36	41.0	1	3.7	48.8	0.50	<0.05	2.72	1.065	0.60	15.8	364
7525		0.7	<0.002	<0.01	0.09	0.4	1	<0.2	84.0	<0.05	<0.05	0.06	0.008	<0.02	0.2	2
7526		115.0	<0.002	0.04	0.31	38.7	<1	1.4	111.5	0.39	<0.05	2.42	0.824	0.78	3.9	311
7527		36.1	<0.002	0.09	0.46	34.4	1	1.0	239	0.21	<0.05	1.75	0.505	0.21	1.1	236
7528		37.3	<0.002	0.10	0.36	35.4	1	1.0	184.5	0.21	<0.05	1.83	0.532	0.21	1.2	251
7529		31.0	0.002	0.11	0.27	33.8	1	0.9	140.5	0.21	<0.05	1.83	0.527	0.17	1.1	246
7530		30.0	<0.002	0.14	0.36	36.0	1	0.9	183.5	0.21	<0.05	1.92	0.519	0.17	1.0	261
7531		1.6	<0.002	0.14	0.46	5.2	<1	0.6	9.7	0.06	<0.05	2.50	0.131	0.04	34.9	71
7532		0.7	<0.002	0.04	0.33	1.0	<1	0.3	4.5	0.12	<0.05	3.85	0.017	<0.02	1.7	11
7533		1.4	<0.002	0.13	0.39	8.0	1	1.0	9.0	0.08	<0.05	0.72	0.198	<0.02	1.3	91
7534		0.7	<0.002	0.18	0.34	0.7	1	<0.2	3.3	<0.05	<0.05	0.39	0.009	<0.02	0.8	6
7535		0.7	<0.002	<0.01	0.36	0.2	<1	<0.2	3.5	<0.05	<0.05	0.03	<0.005	<0.02	0.1	2
7536		0.8	<0.002	0.24	0.39	1.0	1	<0.2	3.2	<0.05	<0.05	0.04	<0.005	<0.02	0.1	20
7537		2.7	<0.002	0.18	0.36	5.7	<1	0.6	5.0	<0.05	<0.05	0.32	0.082	0.02	0.7	59
7538		3.3	<0.002	0.28	0.38	12.3	<1	1.6	8.1	0.09	<0.05	0.79	0.218	0.02	2.0	110
7539		8.6	0.002	1.21	0.36	14.7	1	1.8	7.9	0.11	0.08	0.89	0.270	0.05	1.6	147
7540		7.5	0.002	1.30	0.36	13.8	1	1.5	6.8	0.09	0.08	0.82	0.235	0.05	1.5	132
7541		10.1	0.049	8.49	2.99	8.5	21	2.5	186.0	0.31	3.96	1.08	0.545	0.18	0.4	79
7542		1.0	<0.002	0.25	0.57	1.9	1	0.7	4.2	<0.05	<0.05	0.27	0.009	<0.02	0.9	22

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 7-MAY-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18098245

Sample Description	Method / Analyte / Units / LOR	ME-MS61 W ppm 0.1	ME-MS61 Y ppm 0.1	ME-MS61 Zn ppm 2	ME-MS61 Zr ppm 0.5	Ag-OG62 Ag ppm 1	Cu-OG62 Cu % 0.001	Ni-OG62 Ni % 0.001	CRU-QC Pass2mm % 0.01	PUL-QC Pass75um % 0.01
7503		1.4	7.4	12	93.1				79.1	93.0
7504		1.3	2.7	4	24.2					93.8
7505		0.3	17.7	44	95.2					
7506		0.5	20.7	45	142.5					
7507		0.5	14.9	40	90.6					
7508		0.4	18.6	44	99.0					
7509		0.7	18.0	35	105.5					
7510		0.7	20.8	34	107.0					
7511		0.4	23.7	77	122.5				92.9	
7512		0.3	17.0	135	138.0					
7513		0.3	1.5	12	12.6					
7514		0.5	4.9	11	96.7					
7515		0.5	7.7	11	152.5					
7516		0.4	9.0	124	215					
7517		1.0	9.3	16	109.0					
7518		0.7	7.7	5	161.5					
7519		0.8	13.6	7	192.0					
7520		0.6	34.8	21	145.0					
7521		1.3	43.5	106	192.0					
7522		1.0	27.8	89	157.5					
7523		0.7	42.9	84	153.0					
7524		1.1	36.5	111	166.0					
7525		<0.1	2.0	3	1.7					
7526		0.8	30.6	121	109.5					
7527		0.6	17.3	88	57.2					
7528		0.6	17.5	84	60.5					
7529		0.5	15.4	75	62.0					
7530		0.6	15.8	72	60.3					
7531		0.9	3.8	14	17.1					
7532		0.3	1.0	3	15.3					
7533		0.8	2.9	16	23.8					
7534		0.2	0.3	5	1.5					
7535		<0.1	<0.1	3	<0.5					
7536		0.1	0.1	6	<0.5					
7537		0.7	1.3	13	10.2					
7538		1.0	6.1	19	26.6					
7539		1.5	4.8	26	34.7					
7540		1.1	4.5	24	28.4					
7541		2.5	9.0	144	54.3		1.615	4.58		
7542		0.8	0.3	4	2.6				70.9	85.1

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 7-MAY-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18098245

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	ME-MS61 Ag ppm 0.01	ME-MS61 Al % 0.01	ME-MS61 As ppm 0.2	ME-MS61 Ba ppm 10	ME-MS61 Be ppm 0.05	ME-MS61 Bi ppm 0.01	ME-MS61 Ca % 0.01	ME-MS61 Cd ppm 0.02	ME-MS61 Ce ppm 0.01	ME-MS61 Co ppm 0.1	ME-MS61 Cr ppm 1	ME-MS61 Cs ppm 0.05	ME-MS61 Cu ppm 0.2	ME-MS61 Fe % 0.01
7543		2.27	0.02	0.31	0.6	10	0.42	0.10	0.16	<0.02	0.28	23.6	22	0.12	2.9	4.36
7544		2.01	0.02	0.29	0.5	10	0.41	0.13	0.16	<0.02	0.39	13.4	22	0.08	2.1	1.67
7545		1.35	0.05	0.40	1.4	20	0.42	0.13	0.06	<0.02	0.19	23.6	23	0.12	4.5	2.07
7546		1.46	0.02	3.96	3.0	30	0.89	0.68	0.26	<0.02	2.97	105.0	45	0.23	4.3	6.47
7547		1.17	0.01	6.50	2.0	50	1.67	0.42	0.49	<0.02	6.75	78.2	59	0.52	8.7	12.70
7548		2.50	0.01	6.35	1.2	60	1.41	0.22	0.40	<0.02	8.25	60.1	55	0.64	4.8	12.15
7549		2.06	0.01	6.22	1.2	50	1.28	0.25	0.36	<0.02	5.94	62.2	50	0.55	6.1	11.70
7550		2.02	0.02	5.70	2.8	50	1.12	0.42	0.53	<0.02	11.00	106.5	47	0.55	4.9	12.00
7551		1.00	0.02	4.65	2.4	40	0.90	0.30	0.32	<0.02	18.25	116.0	41	0.35	13.0	8.73
7552		1.09	0.03	3.26	3.2	40	0.46	0.32	0.25	<0.02	16.30	110.0	36	0.31	4.3	4.89
7553		1.98	0.02	7.46	2.7	130	1.02	0.24	6.07	0.03	21.6	53.8	33	0.70	198.5	9.15
7554		1.23	0.04	7.26	1.9	270	0.85	0.15	5.39	0.08	29.0	50.8	41	1.82	98.4	9.49
7555		2.22	0.04	8.08	1.2	690	1.60	0.02	5.30	0.14	68.7	52.6	68	1.38	82.0	11.20
7556		1.94	0.05	8.14	1.5	670	1.47	0.02	5.18	0.15	65.1	53.4	66	1.74	77.1	10.85
7557		1.74	0.03	8.14	0.9	660	1.55	0.02	5.21	0.15	64.7	53.0	67	1.67	77.6	11.00
7558		2.02	0.04	8.02	0.8	660	1.57	0.02	5.14	0.14	67.4	53.2	68	1.86	78.5	10.95
7559		2.31	0.04	7.93	0.5	670	1.39	0.01	5.17	0.11	66.2	50.2	69	1.83	77.5	11.25
7560		2.15	0.03	8.03	0.7	700	1.69	0.02	5.17	0.15	68.8	53.0	65	1.76	80.0	11.15
7561		1.64	0.03	8.00	0.6	680	1.48	0.02	5.20	0.13	64.7	52.7	65	1.59	78.4	11.15
7562		2.49	0.03	7.97	0.8	670	1.45	0.02	5.02	0.12	65.2	52.9	63	1.85	77.1	10.80
7563		2.23	0.05	8.31	0.5	720	1.47	0.02	5.23	0.13	65.9	54.9	70	1.90	79.5	11.25
7564		2.33	0.04	8.20	1.1	670	1.37	0.02	4.96	0.17	63.2	53.9	69	1.71	75.7	10.65
7565		1.91	0.03	8.31	0.8	640	1.26	0.01	4.67	0.15	56.1	55.7	84	1.30	68.9	10.35
7566		1.95	0.06	8.38	1.0	640	1.34	0.01	4.63	0.25	58.2	57.2	81	1.28	74.6	10.25
7567		1.33	0.03	8.18	1.0	670	1.52	0.01	3.67	0.10	62.8	51.7	71	0.75	76.2	10.95
7568		1.14	0.04	7.72	1.0	730	1.61	0.01	3.50	0.05	61.5	52.2	69	0.65	76.5	10.65
7569		0.97	0.04	7.87	1.2	1030	1.42	0.01	2.69	<0.02	65.8	49.7	70	0.71	78.7	10.20
7570		1.33	0.04	7.87	1.0	1110	1.59	0.02	3.22	<0.02	65.8	49.3	67	0.69	78.5	10.50
7571		1.32	0.05	7.23	0.7	1070	1.07	0.02	2.81	<0.02	58.1	46.6	59	0.48	70.3	9.87
7572		2.02	0.03	7.29	1.0	900	1.08	0.02	2.69	0.02	59.2	46.3	60	0.58	66.3	9.35
7573		2.07	0.06	7.56	1.2	1060	1.61	0.02	3.29	0.05	64.0	63.8	65	0.57	77.0	9.16
7574		1.18	0.04	7.15	0.7	730	1.83	0.03	3.09	0.03	61.2	41.0	65	0.44	72.1	8.43
7575		0.72	<0.01	0.09	<0.2	20	0.08	0.01	33.3	<0.02	1.13	1.0	1	<0.05	1.4	0.20
7576		1.18	0.03	6.89	1.7	380	0.95	0.18	4.55	0.02	25.4	44.5	28	0.51	144.0	10.25
7577		1.31	0.03	6.79	2.2	270	0.72	0.19	4.91	<0.02	22.6	43.0	27	0.61	159.0	10.50
7578		1.85	0.03	6.77	3.4	250	0.74	0.19	5.22	<0.02	24.3	48.1	26	0.82	208	9.72
7579		0.89	0.04	6.99	3.3	180	0.70	0.18	5.59	0.03	24.5	56.1	22	0.95	180.5	9.60
7580		0.85	0.03	6.91	3.1	200	0.74	0.18	5.43	0.02	24.0	58.4	22	0.98	172.5	9.72
7581		0.08	3.95	5.40	13.8	110	0.59	0.81	3.40	2.05	17.00	963	266	0.79	>10000	17.65
7582		2.51	0.05	6.84	2.6	130	0.72	0.17	5.18	0.03	24.5	50.7	23	0.65	210	9.44

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 7-MAY-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18098245

Sample Description	Method / Analyte / Units / LOR	ME-MS61 Ga ppm 0.05	ME-MS61 Ge ppm 0.05	ME-MS61 Hf ppm 0.1	ME-MS61 In ppm 0.005	ME-MS61 K % 0.01	ME-MS61 La ppm 0.5	ME-MS61 Li ppm 0.2	ME-MS61 Mg % 0.01	ME-MS61 Mn ppm 5	ME-MS61 Mo ppm 0.05	ME-MS61 Na % 0.01	ME-MS61 Nb ppm 0.1	ME-MS61 Ni ppm 0.2	ME-MS61 P ppm 10	ME-MS61 Pb ppm 0.5
7543		3.52	<0.05	<0.1	0.005	0.10	<0.5	2.4	0.22	61	5.85	0.09	0.1	15.1	<10	2.2
7544		2.96	0.05	<0.1	0.006	0.06	<0.5	2.0	0.21	56	6.91	0.07	0.1	9.5	10	2.3
7545		4.43	<0.05	<0.1	0.006	0.09	<0.5	2.5	0.31	66	8.94	0.07	0.1	15.0	20	2.5
7546		19.60	0.05	0.9	0.023	0.17	1.7	9.5	1.40	166	14.55	2.06	1.7	47.8	180	2.4
7547		31.0	0.09	1.6	0.040	0.33	3.7	14.9	2.42	258	4.94	3.42	2.7	79.2	310	2.1
7548		33.7	0.09	1.6	0.045	0.41	4.8	18.4	3.02	293	6.98	2.82	2.6	85.1	300	1.7
7549		30.8	0.08	1.6	0.035	0.35	3.0	15.4	2.70	287	3.38	2.99	2.5	77.5	290	1.6
7550		28.3	0.09	1.5	0.030	0.36	5.9	12.6	1.86	219	7.22	3.21	2.4	61.3	370	2.7
7551		27.6	0.06	1.1	0.023	0.21	8.4	12.0	1.73	230	16.85	2.41	1.9	71.4	200	2.4
7552		23.2	0.06	0.8	0.017	0.19	7.8	11.8	1.55	279	49.1	1.37	1.7	49.8	170	3.0
7553		21.2	0.09	1.8	0.078	0.41	9.7	34.3	3.94	1160	1.14	2.10	3.5	79.0	390	5.6
7554		19.60	0.11	2.5	0.066	0.74	12.6	47.9	3.66	1210	0.77	1.71	6.0	78.2	900	6.2
7555		25.5	0.16	6.2	0.097	1.14	30.6	15.1	3.01	1540	1.32	2.37	17.5	78.4	3090	13.4
7556		24.9	0.19	5.9	0.090	1.09	28.8	18.2	3.01	1480	1.22	2.33	15.8	88.0	2920	12.8
7557		24.6	0.15	6.0	0.090	1.05	28.8	17.4	3.07	1480	1.24	2.35	15.6	86.3	2930	8.8
7558		25.2	0.15	6.1	0.099	1.07	29.7	18.6	3.01	1480	1.24	2.32	16.1	84.1	2960	8.3
7559		24.7	0.17	6.0	0.092	1.11	28.8	19.5	3.13	1580	1.26	2.28	16.0	73.4	3010	6.4
7560		25.6	0.15	6.2	0.098	1.11	30.4	17.2	3.04	1530	1.32	2.35	17.2	79.3	3040	7.1
7561		24.7	0.16	5.8	0.086	1.06	28.9	16.5	3.16	1520	1.28	2.33	15.8	85.1	2990	6.7
7562		24.8	0.15	6.1	0.090	1.10	29.0	19.0	3.09	1480	1.20	2.25	16.0	85.4	2910	7.4
7563		25.3	0.15	5.9	0.091	1.19	29.4	15.8	3.26	1520	1.24	2.37	15.8	92.4	2950	6.4
7564		24.6	0.19	5.6	0.093	1.12	28.0	16.4	3.25	1450	1.12	2.26	15.2	93.3	2820	11.9
7565		23.7	0.13	4.9	0.077	1.09	24.5	21.8	3.74	1330	1.02	2.04	13.2	109.5	2450	10.3
7566		25.3	0.14	5.3	0.089	1.06	25.2	19.4	3.23	1400	1.15	2.19	14.4	108.0	2630	11.4
7567		26.0	0.16	5.7	0.094	1.33	27.1	29.9	3.70	1580	1.15	2.00	15.4	93.5	2840	3.6
7568		25.3	0.17	6.0	0.087	1.67	25.7	33.7	3.69	1340	1.14	1.85	15.8	88.4	2930	3.7
7569		20.7	0.17	6.2	0.085	4.12	28.2	44.5	3.78	979	1.01	1.27	16.3	82.0	3060	3.5
7570		22.5	0.16	6.1	0.096	3.14	28.5	42.3	3.54	1020	0.96	1.53	16.3	78.2	3030	4.5
7571		23.6	0.16	5.3	0.083	2.71	25.9	50.7	4.07	948	0.79	1.63	14.1	71.5	2600	5.7
7572		23.1	0.15	5.3	0.082	2.33	26.9	38.2	3.71	926	0.72	2.20	13.9	74.6	2580	5.1
7573		22.7	0.16	5.6	0.088	2.56	28.1	35.9	3.41	973	1.02	2.44	15.2	75.4	2850	5.7
7574		21.5	0.13	5.6	0.087	2.30	26.9	30.0	3.43	788	1.04	2.44	15.0	66.0	2800	4.3
7575		0.37	0.11	0.1	<0.005	0.02	1.3	1.2	1.61	85	0.06	0.04	0.1	0.9	60	0.8
7576		19.55	0.10	2.1	0.072	0.83	13.3	34.0	3.83	1540	0.63	2.59	4.6	65.6	520	1.9
7577		20.6	0.09	1.9	0.077	0.58	11.4	34.5	3.76	1650	0.61	2.48	4.3	67.0	440	2.7
7578		19.30	0.09	2.0	0.079	0.60	11.6	38.9	3.54	1320	0.71	1.90	4.4	63.7	510	4.3
7579		18.65	0.10	2.0	0.074	0.59	12.1	35.8	3.23	1280	0.63	1.74	4.3	61.8	440	3.9
7580		18.55	0.08	1.9	0.080	0.59	11.8	37.1	3.27	1320	0.65	1.76	4.0	62.6	410	4.4
7581		11.35	0.39	1.3	0.118	0.30	7.6	8.1	3.93	1000	4.16	1.14	5.0	>10000	450	13.4
7582		18.10	0.09	2.1	0.078	0.55	12.0	21.1	3.05	1240	0.79	1.71	4.0	69.2	450	3.4

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 7-MAY-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18098245

Sample Description	Method / Analyte / Units / LOR	ME-MS61 Rb ppm 0.1	ME-MS61 Re ppm 0.002	ME-MS61 S % 0.01	ME-MS61 Sb ppm 0.05	ME-MS61 Sc ppm 0.1	ME-MS61 Se ppm 1	ME-MS61 Sn ppm 0.2	ME-MS61 Sr ppm 0.2	ME-MS61 Ta ppm 0.05	ME-MS61 Te ppm 0.05	ME-MS61 Th ppm 0.01	ME-MS61 Ti % 0.005	ME-MS61 Tl ppm 0.02	ME-MS61 U ppm 0.1	ME-MS61 V ppm 1
7543		3.3	<0.002	0.23	0.60	1.9	<1	1.0	4.7	<0.05	<0.05	0.03	<0.005	0.03	0.2	26
7544		1.9	<0.002	0.12	0.55	1.4	<1	0.5	4.9	<0.05	<0.05	0.03	<0.005	<0.02	0.1	12
7545		3.5	<0.002	0.21	0.50	2.0	1	0.5	4.0	<0.05	<0.05	0.18	0.005	0.02	1.7	16
7546		7.6	0.002	0.68	0.23	12.3	1	2.1	7.6	0.11	0.06	1.33	0.258	0.04	2.0	117
7547		15.4	<0.002	0.56	0.21	30.7	<1	1.7	14.3	0.18	<0.05	1.54	0.451	0.08	1.8	237
7548		20.0	<0.002	0.41	0.20	30.2	1	1.6	13.8	0.18	<0.05	1.54	0.450	0.11	1.7	227
7549		17.1	0.002	0.39	0.21	27.3	1	1.7	9.7	0.18	<0.05	1.54	0.441	0.10	1.4	235
7550		17.7	<0.002	0.71	0.23	22.7	1	2.3	12.0	0.16	<0.05	1.58	0.397	0.10	1.8	234
7551		10.0	0.002	0.69	0.27	15.7	1	2.7	8.6	0.13	0.05	1.22	0.312	0.05	3.0	178
7552		9.4	0.004	0.73	0.25	9.6	1	1.1	5.9	0.10	0.06	0.76	0.217	0.06	1.8	101
7553		18.9	0.002	0.16	0.51	38.4	1	1.0	250	0.24	<0.05	2.05	0.587	0.10	0.8	273
7554		36.1	<0.002	0.08	0.65	35.5	1	1.1	295	0.37	<0.05	2.08	0.799	0.25	0.7	253
7555		34.3	0.002	0.14	0.29	28.2	1	1.8	418	0.93	<0.05	2.65	1.875	0.25	0.7	240
7556		38.7	<0.002	0.15	0.32	24.9	1	1.7	425	0.88	<0.05	2.50	1.795	0.30	0.7	228
7557		36.2	<0.002	0.15	0.25	25.5	1	1.7	422	0.91	<0.05	2.50	1.795	0.28	0.7	228
7558		38.9	<0.002	0.15	0.27	25.6	1	1.8	416	0.91	<0.05	2.55	1.795	0.32	0.7	232
7559		39.3	<0.002	0.14	0.19	25.3	1	1.8	405	0.91	<0.05	2.50	1.855	0.34	0.7	237
7560		38.4	<0.002	0.14	0.16	28.2	1	1.8	418	0.95	<0.05	2.60	1.865	0.26	0.7	236
7561		33.4	<0.002	0.14	0.14	25.5	1	1.7	419	0.88	<0.05	2.40	1.830	0.24	0.7	230
7562		43.4	<0.002	0.14	0.20	26.5	1	1.7	419	0.93	<0.05	2.52	1.775	0.35	0.7	224
7563		44.6	0.002	0.13	0.14	25.5	1	1.7	445	0.88	<0.05	2.51	1.800	0.28	0.7	233
7564		41.5	0.002	0.14	0.20	23.9	1	1.6	438	0.84	<0.05	2.40	1.755	0.28	0.7	225
7565		44.5	<0.002	0.10	0.24	21.6	1	1.5	457	0.74	<0.05	2.11	1.600	0.28	0.6	219
7566		42.2	<0.002	0.11	0.32	23.4	1	1.6	456	0.81	<0.05	2.28	1.670	0.30	0.6	227
7567		46.0	0.002	0.10	0.27	24.4	1	1.7	409	0.87	<0.05	2.41	1.830	0.25	0.7	240
7568		49.8	<0.002	0.10	0.37	24.3	1	1.7	368	0.91	<0.05	2.33	1.815	0.27	0.7	234
7569		227	<0.002	0.11	0.47	25.3	1	1.8	434	0.93	<0.05	2.58	1.855	1.03	0.7	234
7570		167.0	<0.002	0.13	0.50	25.5	1	1.7	427	0.93	<0.05	2.59	1.850	0.86	0.7	232
7571		113.5	<0.002	0.12	0.44	22.1	1	1.5	247	0.81	<0.05	2.20	1.595	0.61	0.6	200
7572		92.9	<0.002	0.16	0.46	22.0	1	1.5	243	0.82	<0.05	2.19	1.575	0.50	0.6	200
7573		98.7	<0.002	0.30	0.72	24.0	1	1.7	280	0.85	<0.05	2.42	1.740	0.51	0.7	217
7574		92.2	<0.002	0.08	0.60	23.9	1	1.7	295	0.87	<0.05	2.34	1.725	0.50	0.7	213
7575		0.6	<0.002	<0.01	0.10	0.3	1	<0.2	83.0	<0.05	<0.05	0.07	0.012	<0.02	0.1	2
7576		22.9	<0.002	0.05	0.48	33.4	<1	1.0	251	0.33	<0.05	2.42	0.671	0.14	0.7	274
7577		11.3	<0.002	0.05	0.51	34.0	<1	1.0	296	0.32	<0.05	2.44	0.671	0.11	0.8	290
7578		14.6	<0.002	0.10	0.66	33.5	1	1.0	295	0.32	<0.05	2.57	0.689	0.11	0.8	289
7579		26.8	<0.002	0.13	0.84	35.2	1	0.9	296	0.32	<0.05	2.70	0.700	0.11	0.8	296
7580		25.1	0.002	0.13	0.82	35.9	1	0.9	290	0.29	<0.05	2.58	0.683	0.12	0.8	301
7581		10.6	0.043	8.55	3.24	8.3	21	2.4	180.0	0.31	4.35	1.04	0.528	0.16	0.3	78
7582		28.0	<0.002	0.12	0.67	33.9	1	0.9	255	0.30	<0.05	2.77	0.617	0.11	0.8	270

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 7-MAY-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18098245

Sample Description	Method / Analyte / Units / LOR	ME-MS61 W ppm 0.1	ME-MS61 Y ppm 0.1	ME-MS61 Zn ppm 2	ME-MS61 Zr ppm 0.5	Ag-OG62 Ag ppm 1	Cu-OG62 Cu % 0.001	Ni-OG62 Ni % 0.001	CRU-QC Pass2mm % 0.01	PUL-QC Pass75um % 0.01
7543		0.8	0.2	6	<0.5					
7544		0.3	0.3	5	<0.5					
7545		0.4	0.4	7	1.4					
7546		1.1	3.9	19	31.1					
7547		0.9	8.4	29	56.1					
7548		1.1	6.7	34	57.0					
7549		1.1	7.4	32	56.3					
7550		2.3	6.8	25	54.1					
7551		2.0	4.6	26	41.4					
7552		0.7	3.8	28	26.5					
7553		0.7	18.7	69	65.5					
7554		0.6	22.1	83	100.5					
7555		0.3	39.1	168	261					
7556		0.3	37.1	160	250					
7557		0.3	36.7	158	250					
7558		0.3	38.1	159	251					
7559		0.3	37.6	157	257					
7560		0.3	39.0	160	262					
7561		0.3	37.0	159	251					
7562		0.3	37.2	157	250					
7563		0.3	37.4	159	250					
7564		0.3	35.3	170	239					
7565		0.2	31.2	169	208					
7566		0.3	34.4	197	227					
7567		0.3	33.7	131	241					
7568		0.4	34.3	95	248					
7569		0.5	38.5	49	259					
7570		0.5	37.6	56	257					
7571		0.6	33.8	55	221					
7572		0.6	32.5	58	220					
7573		0.8	36.8	75	236					
7574		1.3	37.0	48	236					
7575		0.1	2.0	4	2.2					
7576		0.6	19.4	63	78.2					
7577		0.5	19.2	65	70.9					
7578		0.6	20.5	66	79.0					
7579		0.5	20.5	69	74.8					
7580		0.5	20.1	68	69.3					
7581		2.1	9.5	139	49.5		1.580	4.64		
7582		0.5	20.4	74	77.7				63.6	93.0

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 7-MAY-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18098245

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	ME-MS61 Ag ppm 0.01	ME-MS61 Al % 0.01	ME-MS61 As ppm 0.2	ME-MS61 Ba ppm 10	ME-MS61 Be ppm 0.05	ME-MS61 Bi ppm 0.01	ME-MS61 Ca % 0.01	ME-MS61 Cd ppm 0.02	ME-MS61 Ce ppm 0.01	ME-MS61 Co ppm 0.1	ME-MS61 Cr ppm 1	ME-MS61 Cs ppm 0.05	ME-MS61 Cu ppm 0.2	ME-MS61 Fe % 0.01
7583		2.34	0.02	6.75	2.5	120	0.87	0.18	4.60	0.03	26.6	48.8	10	0.48	116.5	10.45
7584		2.85	0.03	6.91	2.2	110	0.81	0.21	5.09	0.02	20.1	48.3	11	0.48	188.5	10.60
7585		2.41	0.01	7.10	1.7	130	1.12	0.12	4.18	0.02	25.2	44.8	10	0.63	105.0	9.92
7586		2.54	0.02	7.27	2.2	140	1.01	0.19	5.13	0.03	21.7	49.3	7	0.52	140.5	10.10
7587		2.72	0.06	6.15	2.7	100	0.75	0.18	4.63	0.03	24.5	65.2	4	0.40	251	13.35
7588		2.48	0.05	7.14	2.1	120	0.74	0.18	5.19	0.03	22.3	53.0	4	0.47	178.0	10.25
7589		2.44	0.04	7.01	2.5	120	0.73	0.20	5.34	0.04	20.4	50.3	4	0.42	168.5	9.38
7590		2.77	0.03	7.18	2.4	120	0.93	0.23	4.49	0.04	28.4	51.8	5	0.43	117.5	10.75
7591		2.37	0.05	6.49	3.6	120	1.02	0.25	4.39	0.03	30.5	62.4	2	0.35	269	11.90
7592		2.39	0.02	6.54	3.7	150	1.27	0.26	3.27	0.02	34.6	54.9	2	0.38	53.3	12.80
7593		2.58	0.01	6.19	2.4	140	1.25	0.22	3.44	<0.02	34.2	47.5	2	0.52	64.3	12.80
7594		1.77	0.02	6.07	2.1	160	1.08	0.26	4.07	0.02	32.7	51.4	2	0.59	109.5	12.65
7595		1.81	0.01	6.08	2.2	140	1.18	0.21	4.07	<0.02	53.4	51.9	2	0.49	67.6	12.15
7596		1.61	0.02	6.41	2.2	220	1.32	0.24	3.71	<0.02	27.9	56.6	1	0.89	101.5	13.50
7597		2.04	0.02	6.39	1.4	140	1.93	0.14	4.40	0.02	46.3	33.4	2	0.34	7.5	9.54
7598		1.76	0.01	6.09	1.5	30	1.38	0.13	0.90	<0.02	27.5	40.3	6	0.20	2.5	6.88
7599		1.35	0.03	2.49	8.7	10	0.64	0.53	0.27	<0.02	46.0	129.0	12	0.07	2.8	4.64
7600		1.42	0.03	5.69	4.5	10	1.74	0.52	0.73	<0.02	126.5	72.4	11	0.07	3.2	6.20
7601		1.58	0.04	4.65	2.6	20	1.09	0.31	0.62	<0.02	39.1	69.5	9	0.12	2.3	7.22
7602		1.74	0.04	6.14	2.9	30	1.77	0.28	0.90	<0.02	30.7	73.5	6	0.13	4.0	10.15
7603		1.81	0.02	5.86	1.6	80	2.39	0.16	0.80	<0.02	47.3	60.8	5	0.23	2.8	11.60
7604		1.91	0.02	1.65	1.0	10	0.55	0.14	0.20	<0.02	10.90	36.3	16	0.10	2.4	3.28
7605		1.15	0.01	5.62	0.8	20	1.19	0.05	0.49	<0.02	37.5	16.9	9	0.17	2.3	5.24
7606		1.35	0.02	1.05	1.6	10	0.51	0.30	0.17	<0.02	15.50	104.0	14	0.10	4.0	14.85
7607		0.07	>100	5.43	1725	60	0.68	16.30	0.27	13.50	21.2	92.8	36	1.65	>10000	3.70
7608		1.30	0.49	4.66	1.8	20	0.99	0.12	0.27	<0.02	10.75	17.6	14	0.15	22.4	4.00
7609		1.17	0.08	5.29	1.2	10	1.12	0.11	0.51	<0.02	29.4	20.1	10	0.16	5.2	3.62
7610		1.13	0.04	1.60	2.7	10	0.51	0.01	0.15	<0.02	4.15	2.1	27	0.07	3.9	1.08
7611		1.21	0.03	2.77	1.9	10	0.94	0.27	0.42	0.02	11.55	74.1	19	0.07	5.3	5.41
7612		1.38	0.02	5.24	4.1	60	3.08	0.43	0.80	<0.02	24.8	114.0	7	0.15	6.1	16.95
7613		1.34	0.02	5.34	2.5	70	2.46	0.51	0.83	<0.02	29.1	98.8	7	0.26	6.7	15.80
7614		1.11	0.01	5.05	2.2	80	2.22	0.28	0.40	<0.02	30.4	95.9	7	0.35	6.5	13.80
7615		1.31	0.02	5.67	1.8	60	2.30	0.24	0.45	<0.02	45.9	75.8	5	0.27	8.1	12.10
7616		1.21	0.01	1.15	1.2	10	0.69	0.07	0.28	<0.02	9.08	46.6	17	0.12	1.9	7.60
7617		1.76	0.03	5.44	3.4	20	1.12	0.43	1.07	<0.02	27.1	181.5	8	0.10	6.1	13.90
7618		1.36	0.02	6.00	1.5	40	1.77	0.25	0.83	<0.02	44.0	58.7	8	0.23	4.0	7.98
7619		0.60	0.03	4.60	1.7	40	1.75	0.32	0.58	<0.02	46.6	82.1	8	0.31	4.4	9.61
7620		0.63	0.03	5.54	1.7	50	1.97	0.33	0.55	<0.02	51.3	108.5	6	0.37	6.6	12.60
7621		0.07	>100	4.15	1955	490	0.76	159.0	0.33	60.1	25.7	15.7	35	1.76	>10000	2.91
7622		2.34	0.05	4.90	2.8	50	1.62	0.43	1.05	<0.02	47.0	73.0	8	0.18	5.9	10.65

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 7-MAY-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18098245

Sample Description	Method / Analyte / Units / LOR	ME-MS61 Ga ppm 0.05	ME-MS61 Ge ppm 0.05	ME-MS61 Hf ppm 0.1	ME-MS61 In ppm 0.005	ME-MS61 K % 0.01	ME-MS61 La ppm 0.5	ME-MS61 Li ppm 0.2	ME-MS61 Mg % 0.01	ME-MS61 Mn ppm 5	ME-MS61 Mo ppm 0.05	ME-MS61 Na % 0.01	ME-MS61 Nb ppm 0.1	ME-MS61 Ni ppm 0.2	ME-MS61 P ppm 10	ME-MS61 Pb ppm 0.5
7583		18.60	0.10	2.2	0.079	0.58	13.1	16.2	2.83	1300	0.66	1.94	4.9	47.5	490	3.2
7584		19.10	0.09	1.4	0.082	0.59	10.0	16.4	3.17	1340	0.61	1.77	3.4	59.2	360	3.2
7585		25.2	0.10	1.7	0.135	0.82	10.8	22.3	3.88	1240	0.35	2.23	3.5	61.5	330	2.5
7586		20.3	0.10	1.7	0.095	0.77	10.3	17.4	3.27	1380	0.50	1.93	3.4	50.7	350	3.8
7587		20.2	0.10	1.8	0.084	0.60	11.8	15.3	3.00	1500	0.71	1.55	4.4	59.1	440	3.5
7588		19.70	0.09	1.7	0.080	0.74	10.9	17.1	3.14	1450	0.52	1.63	3.7	51.2	390	4.0
7589		18.25	0.09	1.5	0.069	0.71	10.0	16.7	3.08	1440	0.50	1.48	3.4	49.8	360	4.5
7590		20.4	0.10	1.9	0.081	0.67	14.6	18.8	3.16	1340	0.69	1.86	4.2	46.5	410	3.8
7591		21.4	0.10	2.4	0.104	0.54	14.6	15.4	2.27	1200	0.97	2.29	5.1	32.7	560	4.6
7592		22.4	0.10	3.1	0.093	0.67	17.1	17.1	2.09	1180	0.83	2.64	6.4	21.9	640	3.9
7593		22.1	0.11	2.8	0.143	0.79	16.3	17.4	2.09	1210	0.62	2.52	5.9	22.7	610	3.3
7594		21.3	0.11	2.3	0.117	0.92	16.5	19.0	2.06	1300	0.62	2.08	5.2	20.8	530	3.1
7595		21.9	0.13	2.4	0.111	0.74	30.2	24.8	2.39	1240	0.78	2.31	5.3	20.6	520	2.6
7596		22.8	0.11	2.1	0.126	1.36	13.5	26.2	2.26	1160	0.66	2.20	5.1	22.0	500	3.0
7597		26.3	0.12	3.6	0.074	0.60	21.9	20.0	2.01	686	1.06	3.03	6.4	21.1	570	3.2
7598		32.4	0.09	4.8	0.046	0.20	14.1	19.2	2.20	322	5.64	3.20	6.3	33.1	510	2.5
7599		13.95	0.08	2.0	0.019	0.06	24.4	7.8	0.83	109	13.85	1.32	2.2	20.4	360	2.3
7600		24.2	0.16	6.0	0.029	0.06	64.2	10.6	1.16	153	9.75	3.61	5.5	22.4	720	3.0
7601		20.5	0.08	3.6	0.021	0.12	20.0	10.3	1.12	145	31.3	2.84	4.6	23.5	960	2.6
7602		19.60	0.10	5.0	0.018	0.17	16.3	4.9	0.44	109	17.15	4.54	4.7	12.0	1480	5.5
7603		24.6	0.12	5.1	0.028	0.35	25.3	10.1	0.87	171	2.32	3.75	5.9	16.6	1550	3.6
7604		8.86	<0.05	1.2	0.010	0.08	5.7	4.7	0.46	77	4.06	0.96	1.5	13.9	310	2.3
7605		21.1	0.08	4.7	0.018	0.18	19.5	9.0	0.90	115	4.90	3.91	2.7	18.4	1460	3.4
7606		6.52	0.08	0.6	0.012	0.08	7.9	3.1	0.29	83	4.56	0.63	0.6	11.4	110	1.8
7607		32.7	0.25	2.7	4.13	1.01	10.3	23.3	0.04	99	5.36	0.55	7.1	1540	510	1445
7608		19.25	0.05	3.4	0.014	0.13	4.9	9.5	0.97	104	2.63	3.03	1.9	19.3	620	3.5
7609		22.5	0.08	4.1	0.018	0.10	15.0	11.0	1.21	122	17.55	3.43	3.0	21.2	1170	3.7
7610		6.10	<0.05	1.1	<0.005	0.04	2.0	2.4	0.24	62	2.10	1.10	1.2	5.9	260	3.1
7611		10.85	0.07	1.8	0.010	0.07	5.8	4.4	0.36	70	11.00	1.97	1.9	15.1	620	5.8
7612		16.95	0.11	3.6	0.028	0.28	11.7	7.1	0.33	101	5.12	3.82	2.5	13.0	720	5.3
7613		23.5	0.12	3.5	0.038	0.40	13.9	12.4	0.83	150	4.45	3.39	2.2	16.2	720	3.7
7614		26.6	0.11	3.2	0.037	0.48	14.9	19.6	1.39	185	5.25	2.67	1.5	22.8	680	3.0
7615		31.2	0.12	3.8	0.041	0.38	24.2	22.3	1.73	196	8.54	3.09	1.7	32.8	780	3.2
7616		7.04	0.05	0.5	0.010	0.09	4.9	4.9	0.35	81	5.72	0.67	0.5	12.4	140	2.4
7617		15.25	0.10	3.9	0.017	0.13	13.1	3.5	0.16	98	4.96	4.38	3.1	15.3	790	7.7
7618		20.5	0.09	4.1	0.021	0.30	23.4	8.0	0.56	105	11.60	4.41	2.5	13.3	760	5.2
7619		25.1	0.10	3.2	0.036	0.34	25.0	20.9	1.68	186	73.5	2.30	2.0	24.7	560	3.2
7620		30.6	0.11	4.1	0.041	0.42	27.5	23.1	1.85	211	39.1	2.99	1.7	28.5	730	3.6
7621		24.3	0.19	2.7	12.45	0.62	10.3	21.1	0.08	144	6.92	0.43	7.7	117.0	560	2060
7622		22.1	0.09	3.6	0.030	0.26	24.2	14.1	1.10	153	30.4	2.98	3.1	16.0	650	4.0

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 7-MAY-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18098245

Sample Description	Method / Analyte / Units / LOR	ME-MS61 Rb ppm 0.1	ME-MS61 Re ppm 0.002	ME-MS61 S % 0.01	ME-MS61 Sb ppm 0.05	ME-MS61 Sc ppm 0.1	ME-MS61 Se ppm 1	ME-MS61 Sn ppm 0.2	ME-MS61 Sr ppm 0.2	ME-MS61 Ta ppm 0.05	ME-MS61 Te ppm 0.05	ME-MS61 Th ppm 0.01	ME-MS61 Ti % 0.005	ME-MS61 Tl ppm 0.02	ME-MS61 U ppm 0.1	ME-MS61 V ppm 1
7583		30.1	0.002	0.11	0.62	35.9	1	1.1	206	0.36	<0.05	3.06	0.830	0.11	0.9	307
7584		29.7	<0.002	0.11	0.55	38.3	1	0.8	213	0.25	<0.05	2.22	0.796	0.10	0.6	429
7585		31.5	0.002	0.07	0.39	38.7	1	1.6	138.5	0.26	<0.05	2.12	0.685	0.15	1.4	364
7586		41.4	0.002	0.11	0.49	39.3	1	1.1	190.5	0.25	<0.05	2.25	0.668	0.13	0.8	395
7587		32.3	0.002	0.13	0.63	45.7	1	1.1	181.0	0.31	<0.05	2.66	1.175	0.11	0.8	800
7588		41.1	0.002	0.09	0.58	39.1	<1	0.9	229	0.26	<0.05	2.36	0.700	0.13	0.7	377
7589		37.3	<0.002	0.11	0.59	36.0	1	0.9	244	0.26	<0.05	2.20	0.590	0.13	0.7	305
7590		36.5	<0.002	0.09	0.56	37.3	<1	1.1	240	0.30	<0.05	2.74	0.716	0.12	0.9	332
7591		28.3	0.002	0.19	0.62	38.7	1	1.3	226	0.36	<0.05	3.36	1.060	0.10	1.0	580
7592		35.2	0.003	0.18	0.52	39.7	1	1.3	159.5	0.47	<0.05	3.95	1.315	0.10	1.2	561
7593		43.6	0.002	0.13	0.47	41.0	1	1.5	160.0	0.44	<0.05	3.85	1.285	0.14	1.4	598
7594		50.5	0.003	0.14	0.50	39.4	1	1.3	202	0.39	<0.05	3.62	1.270	0.17	1.1	578
7595		40.1	0.004	0.15	0.37	41.2	1	1.3	142.0	0.40	<0.05	3.32	1.365	0.13	1.2	601
7596		76.2	0.004	0.18	0.38	44.2	1	1.1	177.0	0.38	<0.05	3.11	1.430	0.26	1.0	703
7597		29.7	<0.002	0.24	0.24	38.7	1	2.4	94.0	0.49	<0.05	4.73	1.410	0.09	3.1	476
7598		10.8	0.002	0.32	0.24	33.9	1	2.8	20.5	0.50	<0.05	5.13	1.005	0.05	5.7	179
7599		2.6	0.002	0.83	0.27	10.1	1	1.1	8.5	0.17	0.05	2.47	0.230	0.02	4.7	65
7600		2.4	<0.002	0.50	0.24	20.6	1	1.9	19.9	0.47	0.05	7.61	0.501	0.02	7.2	78
7601		5.9	0.002	0.45	0.21	13.1	1	2.6	16.2	0.33	<0.05	4.35	0.387	0.03	6.5	86
7602		7.7	0.002	0.57	0.33	17.7	1	3.1	30.0	0.37	<0.05	6.08	0.483	0.04	7.6	53
7603		18.5	<0.002	0.47	0.28	24.1	<1	2.8	42.1	0.51	<0.05	6.48	0.695	0.06	4.0	37
7604		3.6	<0.002	0.25	0.35	6.5	1	1.0	8.2	0.11	<0.05	1.45	0.148	0.02	3.2	32
7605		8.0	<0.002	0.12	0.21	19.5	<1	1.2	18.6	0.24	<0.05	5.78	0.381	0.03	6.8	54
7606		3.6	<0.002	0.54	0.33	8.5	1	4.8	6.4	<0.05	<0.05	0.78	0.048	0.02	3.2	87
7607		30.3	0.002	8.48	313	5.1	82	2.8	349	0.56	35.2	4.31	0.181	15.40	2.7	40
7608		6.3	<0.002	0.09	0.36	14.2	<1	1.1	14.0	0.15	<0.05	3.95	0.240	0.04	6.4	64
7609		4.4	<0.002	0.11	0.24	18.4	1	1.5	17.8	0.25	<0.05	5.14	0.419	0.02	7.2	51
7610		1.2	<0.002	0.01	0.32	4.5	<1	0.4	9.4	0.09	<0.05	1.31	0.147	<0.02	1.4	14
7611		2.8	<0.002	0.49	0.35	11.7	1	1.7	13.5	0.12	<0.05	2.13	0.263	0.02	4.2	50
7612		12.9	<0.002	0.83	0.35	26.5	1	1.9	49.8	0.21	<0.05	4.12	0.492	0.04	4.9	53
7613		20.5	<0.002	0.73	0.30	26.5	1	1.8	57.3	0.21	<0.05	4.10	0.575	0.07	3.0	89
7614		25.2	<0.002	0.62	0.29	22.2	1	1.2	47.8	0.17	<0.05	3.78	0.497	0.10	2.5	67
7615		19.8	0.002	0.49	0.27	27.3	1	1.4	45.8	0.18	<0.05	4.36	0.551	0.08	3.9	79
7616		4.2	<0.002	0.26	0.44	7.6	1	1.3	7.6	<0.05	<0.05	0.63	0.077	0.02	1.3	53
7617		5.2	<0.002	1.15	0.31	22.1	2	2.6	28.3	0.23	0.05	4.58	0.510	0.03	8.8	101
7618		14.6	0.003	0.41	0.24	19.8	1	1.8	33.3	0.21	<0.05	4.77	0.509	0.06	6.0	78
7619		18.8	0.007	0.58	0.26	36.8	1	1.8	27.0	0.21	<0.05	3.66	0.529	0.07	2.6	85
7620		22.1	0.002	0.77	0.26	29.3	1	1.5	34.2	0.21	<0.05	4.73	0.547	0.09	3.0	98
7621		23.2	0.002	3.88	221	4.3	64	13.4	476	0.56	61.1	5.35	0.208	4.45	2.8	33
7622		13.0	0.002	0.55	0.34	28.2	1	2.0	37.8	0.29	0.05	4.19	0.669	0.05	2.9	85

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 7-MAY-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18098245

Sample Description	Method Analyte Units LOR	ME-MS61 W ppm 0.1	ME-MS61 Y ppm 0.1	ME-MS61 Zn ppm 2	ME-MS61 Zr ppm 0.5	Ag-OG62 Ag ppm 1	Cu-OG62 Cu % 0.001	Ni-OG62 Ni % 0.001	CRU-QC Pass2mm % 0.01	PUL-QC Pass75um % 0.01
7583		0.5	22.2	73	86.0					
7584		0.5	17.5	80	53.4					
7585		0.5	18.9	101	64.2					
7586		0.4	18.5	89	61.5					
7587		0.6	21.8	91	70.2					
7588		0.5	19.2	94	65.3					
7589		0.5	17.9	93	57.2					
7590		0.6	21.0	91	72.3					
7591		0.7	25.1	65	91.7					
7592		0.7	27.4	63	114.5					
7593		0.6	27.6	61	115.0					
7594		0.7	25.3	64	91.0					
7595		0.8	25.9	60	90.1					
7596		0.7	23.7	55	84.5					
7597		1.0	32.0	39	130.0					
7598		1.2	25.0	36	171.5					
7599		0.7	5.6	14	75.0					
7600		1.0	25.2	21	228					
7601		1.0	12.4	20	136.0					
7602		1.8	27.3	11	184.0					
7603		1.6	31.7	18	188.5					97.0
7604		0.7	4.6	9	45.5					97.3
7605		0.9	16.0	15	173.5					
7606		3.0	2.4	7	24.7					
7607		27.4	4.4	2190	92.8	992	5.03			
7608		0.9	10.0	15	126.5					
7609		1.0	14.0	17	151.5					
7610		0.3	3.5	6	39.6				82.0	
7611		0.9	13.1	9	66.2					
7612		2.1	31.3	8	130.0					
7613		1.7	24.5	13	129.5					
7614		0.6	14.4	19	117.0					
7615		0.7	22.6	22	138.5					
7616		1.1	4.3	7	18.8					
7617		1.7	16.3	7	141.0					
7618		0.9	19.3	10	149.5					
7619		0.6	25.6	23	117.5					
7620		0.7	20.0	26	148.0					
7621		16.3	5.9	9410	90.3	296	1.010			
7622		0.7	25.5	18	129.0				75.2	98.2

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 7-MAY-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18098245

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	ME-MS61 Ag ppm 0.01	ME-MS61 Al % 0.01	ME-MS61 As ppm 0.2	ME-MS61 Ba ppm 10	ME-MS61 Be ppm 0.05	ME-MS61 Bi ppm 0.01	ME-MS61 Ca % 0.01	ME-MS61 Cd ppm 0.02	ME-MS61 Ce ppm 0.01	ME-MS61 Co ppm 0.1	ME-MS61 Cr ppm 1	ME-MS61 Cs ppm 0.05	ME-MS61 Cu ppm 0.2	ME-MS61 Fe % 0.01
7623		2.19	0.04	5.72	2.1	40	1.81	0.30	1.12	<0.02	30.8	56.1	7	0.13	5.1	9.33
7624		1.66	0.02	4.17	2.1	20	2.05	0.35	0.93	<0.02	15.85	128.5	14	0.17	3.1	5.67
7625		0.82	0.01	0.06	<0.2	20	0.05	0.01	31.9	<0.02	0.84	1.8	3	<0.05	2.3	0.12
7626		1.20	0.04	3.54	1.5	20	0.69	0.18	1.09	<0.02	14.75	42.3	14	0.15	3.3	6.43
7627		1.23	0.01	5.60	2.7	160	2.68	0.19	3.82	<0.02	54.4	29.2	5	0.20	12.6	9.99
7628		2.12	0.01	6.11	2.6	110	2.23	0.24	1.95	<0.02	76.6	49.8	5	0.24	11.7	11.80
7629		2.10	0.01	5.27	1.9	70	1.53	0.24	1.20	<0.02	79.5	49.8	7	0.35	27.8	10.55
7630		2.34	0.05	6.06	3.5	120	1.52	0.32	2.69	<0.02	39.2	59.0	3	0.48	87.3	13.05
7631		2.14	0.01	6.14	3.7	110	1.34	0.27	3.01	0.02	40.3	60.4	2	0.32	68.6	13.40
7632		2.18	0.03	5.25	3.2	60	1.26	0.67	1.60	<0.02	55.1	72.1	7	0.44	23.9	11.20
7633		2.42	0.01	5.52	3.6	80	1.01	0.37	1.81	0.02	52.2	129.5	5	0.37	18.4	10.95
7634		2.37	0.01	6.01	3.0	160	1.42	0.27	2.83	<0.02	36.1	60.2	2	0.59	73.1	13.25
7635		2.31	0.02	6.17	3.3	110	1.24	0.23	3.11	0.02	39.7	54.5	2	0.27	62.1	12.15
7636		2.36	0.02	6.16	4.8	130	1.38	0.25	3.34	0.03	43.7	58.0	2	0.42	40.6	11.45
7637		1.53	0.01	6.14	4.1	150	1.72	0.26	3.32	0.02	42.6	53.6	2	0.47	48.7	12.45
7638		1.15	0.01	0.21	0.4	10	0.23	0.04	0.32	<0.02	1.25	8.7	17	0.05	2.5	1.56
7639		1.82	0.03	5.86	2.9	150	1.28	0.34	2.87	0.03	34.4	61.9	4	0.61	98.7	13.15
7640		2.46	0.03	6.01	2.8	160	1.20	0.30	2.68	0.03	34.3	63.4	3	0.62	115.0	13.75
7641		2.36	0.03	6.03	3.6	110	0.83	0.17	3.24	<0.02	36.9	50.9	3	0.20	91.1	10.90
7642		2.32	0.02	6.09	2.9	130	1.21	0.23	2.64	<0.02	38.3	58.8	3	0.28	108.0	11.85
7643		1.53	0.03	6.11	3.4	140	1.45	0.25	3.62	0.02	43.7	49.7	4	0.25	90.9	11.95
7644		1.08	0.04	3.44	1.4	40	0.79	0.49	1.24	<0.02	20.6	77.2	9	0.11	10.5	5.81
7645		2.15	0.02	5.66	2.0	100	2.23	0.28	0.75	<0.02	46.1	66.5	4	0.45	14.2	13.75
7646		2.22	0.02	5.63	2.1	70	1.32	0.29	1.90	<0.02	43.0	94.9	4	0.35	11.2	11.45
7647		2.00	0.02	6.45	2.0	70	1.05	0.22	1.00	<0.02	69.4	63.9	2	0.43	16.5	12.00
7648		1.19	0.03	5.93	2.3	50	0.88	0.22	0.82	<0.02	43.3	79.5	8	0.29	13.0	11.75
7649		1.93	0.02	1.28	0.5	20	0.30	0.08	0.20	<0.02	5.39	17.2	17	0.11	2.3	2.69
7650		1.39	0.01	5.61	1.7	100	1.19	0.26	1.14	<0.02	48.4	77.2	7	0.24	17.8	10.35
7651		2.55	0.01	5.99	2.3	110	1.35	0.24	2.14	0.02	59.9	59.9	4	0.25	25.4	11.85
7652		2.23	0.01	5.30	1.3	70	1.15	0.25	0.79	<0.02	55.1	77.8	5	0.20	10.4	10.85
7653		2.31	0.03	6.00	2.0	140	1.29	0.32	3.14	<0.02	37.1	61.6	3	0.41	163.0	12.95
7654		2.36	0.02	5.62	0.9	110	1.39	0.18	2.16	<0.02	46.7	48.2	4	0.42	62.8	12.75
7655		2.24	0.03	5.75	1.2	100	1.39	0.20	2.06	<0.02	38.4	46.8	4	0.39	117.0	12.65
7656		2.36	0.02	6.24	1.4	120	1.74	0.30	2.62	<0.02	47.0	47.4	4	0.34	87.2	12.35
7657		1.98	0.02	3.66	1.3	20	0.80	0.29	0.36	<0.02	41.8	66.3	12	0.13	7.1	8.14
7658		1.43	0.01	5.59	1.3	40	1.35	0.32	1.01	<0.02	65.8	44.7	8	0.19	55.1	11.75
7659		0.66	0.02	5.81	0.9	60	1.48	0.20	0.83	<0.02	53.8	48.0	5	0.26	27.4	12.60
7660		0.66	0.01	5.79	0.7	70	1.47	0.20	0.67	<0.02	58.5	46.2	5	0.28	25.4	12.50
7661		0.08	4.07	5.40	12.9	120	0.61	0.87	3.37	2.00	18.00	953	259	0.76	>10000	17.50
7662		1.01	0.01	0.30	0.3	10	0.36	0.04	0.03	<0.02	0.48	7.5	17	0.06	10.3	0.82

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 7-MAY-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18098245

Sample Description	Method / Analyte / Units / LOR	ME-MS61 Ga ppm 0.05	ME-MS61 Ge ppm 0.05	ME-MS61 Hf ppm 0.1	ME-MS61 In ppm 0.005	ME-MS61 K % 0.01	ME-MS61 La ppm 0.5	ME-MS61 Li ppm 0.2	ME-MS61 Mg % 0.01	ME-MS61 Mn ppm 5	ME-MS61 Mo ppm 0.05	ME-MS61 Na % 0.01	ME-MS61 Nb ppm 0.1	ME-MS61 Ni ppm 0.2	ME-MS61 P ppm 10	ME-MS61 Pb ppm 0.5
7623		22.5	0.10	4.1	0.023	0.21	14.5	11.2	0.92	139	10.40	3.86	3.7	15.7	750	4.4
7624		14.45	0.07	2.7	0.014	0.18	7.7	6.0	0.48	109	14.80	2.98	2.6	13.3	520	4.0
7625		0.23	<0.05	<0.1	<0.005	0.01	1.0	1.4	1.82	77	0.28	0.03	0.1	0.3	60	<0.5
7626		12.20	0.06	2.3	0.013	0.18	7.3	3.3	0.28	114	17.80	2.64	2.3	6.8	470	4.3
7627		24.2	0.11	3.9	0.057	0.58	28.1	15.9	1.16	373	2.98	2.77	5.7	7.2	710	3.9
7628		26.6	0.12	4.3	0.046	0.48	41.2	18.5	1.48	331	1.73	3.23	5.6	13.1	760	3.8
7629		24.2	0.12	3.6	0.042	0.42	44.0	18.9	1.56	337	4.79	2.67	5.3	18.2	620	3.2
7630		22.8	0.11	3.4	0.115	0.68	18.3	21.2	1.55	802	0.93	2.48	6.3	7.2	670	3.7
7631		23.2	0.11	3.4	0.136	0.58	18.9	20.6	1.55	926	1.11	2.44	6.5	7.5	660	4.0
7632		23.0	0.09	3.2	0.073	0.43	29.8	14.7	1.39	507	4.77	2.67	5.5	16.7	580	3.0
7633		28.0	0.11	3.2	0.063	0.48	27.1	21.8	2.01	766	6.03	2.36	5.5	26.0	610	3.1
7634		22.2	0.11	2.9	0.103	0.95	16.4	22.8	1.66	1080	0.88	2.15	6.0	9.0	620	3.6
7635		23.1	0.10	3.4	0.095	0.53	19.6	22.0	1.74	1050	1.14	2.62	6.1	11.0	660	4.2
7636		25.8	0.11	3.4	0.098	0.71	20.9	27.4	2.09	948	1.22	2.43	6.2	15.5	630	5.0
7637		25.6	0.09	3.3	0.096	0.79	21.6	27.3	1.99	865	6.01	2.38	6.1	16.4	610	5.0
7638		1.34	<0.05	0.1	<0.005	0.06	0.6	1.5	0.09	83	3.95	0.06	0.1	3.4	10	1.8
7639		23.1	0.10	2.7	0.099	0.98	15.3	24.2	1.66	1100	3.77	2.12	5.7	15.6	590	4.0
7640		22.9	0.11	2.8	0.111	1.07	15.0	25.8	1.75	1140	0.87	2.17	5.9	15.1	600	3.9
7641		21.8	0.08	3.1	0.073	0.47	18.5	15.8	1.22	876	1.99	3.26	5.2	14.1	620	4.3
7642		23.9	0.09	3.1	0.080	0.63	19.3	23.1	1.79	873	1.15	2.65	5.6	19.0	600	5.5
7643		24.7	0.10	3.2	0.082	0.55	22.0	22.2	1.74	752	1.34	2.68	5.6	18.6	630	4.8
7644		14.70	0.06	1.8	0.023	0.20	10.5	9.0	0.80	224	41.0	1.99	2.3	19.0	340	3.4
7645		27.8	0.10	3.0	0.032	0.57	25.4	22.2	1.76	287	4.78	2.89	4.0	35.5	520	3.9
7646		31.2	0.10	3.0	0.042	0.48	23.1	28.0	2.57	466	7.45	2.39	4.1	42.7	530	2.8
7647		32.3	0.18	3.2	0.039	0.60	37.4	31.1	2.71	468	1.29	2.95	4.4	45.4	520	3.7
7648		29.5	0.14	2.9	0.029	0.37	23.5	23.7	2.12	349	4.25	3.02	4.0	43.4	530	3.7
7649		8.89	0.06	0.6	0.007	0.12	2.8	6.1	0.66	106	12.95	0.50	1.0	15.9	100	2.8
7650		26.7	0.14	2.8	0.032	0.49	26.7	18.2	1.63	309	6.14	2.87	3.9	39.3	480	3.4
7651		28.2	0.15	3.3	0.040	0.55	32.2	22.7	1.86	391	1.88	2.94	4.7	44.5	530	3.7
7652		26.2	0.14	2.6	0.028	0.40	29.8	16.9	1.54	314	4.08	2.73	3.9	39.4	480	3.2
7653		23.5	0.14	2.6	0.096	0.78	18.1	25.6	1.92	716	0.98	2.42	5.1	38.0	520	3.5
7654		27.1	0.14	2.9	0.055	0.67	24.1	28.0	2.25	410	2.73	2.35	4.4	46.6	530	2.8
7655		23.5	0.14	2.8	0.067	0.62	19.1	25.5	2.06	446	1.48	2.52	4.5	41.4	500	2.5
7656		26.0	0.14	2.9	0.065	0.66	25.4	24.1	1.76	417	1.63	2.93	4.7	41.8	550	3.2
7657		19.40	0.10	1.7	0.018	0.17	22.6	12.5	1.32	165	6.68	1.89	2.6	35.6	320	2.7
7658		27.7	0.13	2.8	0.038	0.30	34.6	19.7	1.97	155	3.31	2.88	4.3	55.2	490	3.0
7659		27.9	0.13	2.8	0.036	0.44	29.3	22.8	2.03	219	3.31	2.91	3.5	51.6	520	2.7
7660		27.7	0.15	2.8	0.034	0.47	31.7	23.4	1.99	207	3.17	2.91	3.5	50.7	530	2.8
7661		11.80	0.55	1.2	0.116	0.30	7.6	8.6	3.90	978	4.45	1.14	5.1	>10000	460	15.0
7662		2.50	<0.05	0.1	<0.005	0.04	<0.5	2.1	0.20	51	3.73	0.07	0.1	19.3	10	1.3

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 7-MAY-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18098245

Sample Description	Method / Analyte / Units / LOR	ME-MS61 Rb ppm 0.1	ME-MS61 Re ppm 0.002	ME-MS61 S % 0.01	ME-MS61 Sb ppm 0.05	ME-MS61 Sc ppm 0.1	ME-MS61 Se ppm 1	ME-MS61 Sn ppm 0.2	ME-MS61 Sr ppm 0.2	ME-MS61 Ta ppm 0.05	ME-MS61 Te ppm 0.05	ME-MS61 Th ppm 0.01	ME-MS61 Ti % 0.005	ME-MS61 Tl ppm 0.02	ME-MS61 U ppm 0.1	ME-MS61 V ppm 1
7623		9.5	<0.002	0.40	0.28	32.2	1	2.4	36.4	0.30	<0.05	4.64	0.712	0.04	3.7	97
7624		8.8	0.002	0.84	0.36	20.9	1	1.5	18.5	0.19	0.05	3.13	0.419	0.05	3.2	61
7625		0.3	<0.002	<0.01	0.08	0.4	1	<0.2	80.7	<0.05	<0.05	0.07	0.006	<0.02	0.2	1
7626		8.2	0.002	0.28	0.31	13.2	1	1.3	18.1	0.18	<0.05	2.77	0.438	0.04	2.8	100
7627		27.3	0.005	0.26	0.28	35.3	1	1.9	93.0	0.44	<0.05	4.46	1.045	0.07	2.2	206
7628		21.7	0.006	0.35	0.27	34.4	1	2.3	59.1	0.45	<0.05	4.98	1.125	0.08	2.4	251
7629		21.0	0.005	0.35	0.27	26.2	1	2.3	41.1	0.40	<0.05	4.12	1.010	0.07	2.2	241
7630		35.4	0.006	0.22	0.55	39.0	1	1.5	164.0	0.46	<0.05	4.62	1.280	0.12	1.5	359
7631		29.5	0.006	0.23	0.60	39.8	1	1.6	174.0	0.46	<0.05	4.41	1.330	0.11	1.4	375
7632		22.2	0.007	0.41	0.47	30.3	1	1.9	82.2	0.40	<0.05	3.75	1.120	0.10	2.0	324
7633		24.0	0.005	0.89	0.37	29.8	1	1.8	71.4	0.40	<0.05	3.80	1.180	0.09	2.3	370
7634		51.5	0.009	0.23	0.29	38.3	1	1.4	164.0	0.42	<0.05	3.93	1.330	0.18	1.3	433
7635		25.1	0.007	0.25	0.29	38.8	1	1.6	109.0	0.42	<0.05	4.03	1.340	0.09	1.5	446
7636		38.6	0.007	0.27	0.27	40.0	2	2.4	90.3	0.44	<0.05	4.03	1.360	0.13	2.0	475
7637		41.4	0.006	0.32	0.27	40.0	1	1.8	95.0	0.45	<0.05	3.94	1.430	0.13	1.6	537
7638		1.5	<0.002	0.07	0.32	1.4	1	0.4	5.4	<0.05	<0.05	0.06	0.021	0.02	0.1	34
7639		53.7	0.005	0.22	0.32	38.3	1	1.6	140.5	0.42	<0.05	3.72	1.430	0.19	1.3	621
7640		60.9	0.005	0.19	0.35	39.0	1	1.5	136.0	0.41	<0.05	3.85	1.420	0.20	1.2	609
7641		21.5	0.005	0.20	0.29	35.7	1	1.7	65.3	0.38	<0.05	3.77	1.250	0.06	1.8	504
7642		32.7	0.002	0.23	0.28	35.7	1	1.8	81.4	0.41	<0.05	3.73	1.400	0.09	1.7	622
7643		26.3	0.002	0.23	0.26	39.4	1	1.8	84.1	0.40	<0.05	3.76	1.300	0.08	1.6	599
7644		8.8	0.005	0.45	0.24	15.5	1	1.7	19.6	0.17	0.14	2.01	0.625	0.04	2.2	305
7645		28.1	0.003	0.45	0.26	36.0	1	2.0	31.1	0.31	<0.05	3.28	1.180	0.09	2.3	674
7646		24.0	0.005	0.61	0.25	35.2	1	2.1	32.5	0.31	0.05	3.38	1.160	0.10	2.4	684
7647		32.7	0.002	0.35	0.26	36.5	1	2.2	22.2	0.35	<0.05	3.75	1.245	0.11	3.1	759
7648		19.4	0.003	0.50	0.25	30.5	1	2.4	18.6	0.31	<0.05	3.37	1.125	0.07	3.0	709
7649		5.3	0.003	0.11	0.27	5.8	<1	0.6	5.3	0.06	<0.05	0.76	0.233	0.03	2.0	145
7650		22.8	0.003	0.50	0.25	30.6	1	1.8	31.6	0.30	<0.05	3.30	1.075	0.08	2.9	653
7651		26.2	0.002	0.33	0.28	34.8	1	2.6	44.1	0.37	<0.05	3.70	1.365	0.08	2.7	894
7652		19.0	0.002	0.47	0.24	27.8	1	2.3	28.8	0.29	<0.05	3.15	1.105	0.06	2.5	735
7653		38.9	0.003	0.22	0.33	37.9	1	1.5	132.5	0.38	<0.05	3.52	1.240	0.12	1.4	816
7654		33.4	0.003	0.24	0.23	34.7	1	1.6	62.0	0.35	<0.05	3.52	1.145	0.11	1.6	793
7655		30.2	0.004	0.17	0.25	35.1	1	1.5	84.1	0.35	<0.05	3.45	1.120	0.11	1.3	755
7656		30.5	<0.002	0.24	0.27	36.4	1	1.6	97.9	0.37	<0.05	3.61	1.105	0.10	2.0	685
7657		7.2	<0.002	0.44	0.27	19.7	1	1.4	13.6	0.19	<0.05	2.10	0.628	0.04	1.5	429
7658		13.5	0.003	0.26	0.34	33.4	1	1.9	38.5	0.32	<0.05	3.30	1.020	0.05	2.1	691
7659		20.4	0.002	0.27	0.26	33.5	1	1.6	51.1	0.30	<0.05	3.44	0.943	0.06	2.2	666
7660		21.6	0.002	0.27	0.25	33.0	1	1.6	50.9	0.30	<0.05	3.41	0.948	0.07	2.1	672
7661		10.8	0.042	8.46	3.01	8.5	22	2.9	179.5	0.32	4.56	1.08	0.526	0.18	0.3	78
7662		1.1	<0.002	0.05	0.57	1.0	<1	<0.2	5.2	<0.05	<0.05	0.07	0.017	0.02	0.5	20

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 7-MAY-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18098245

Sample Description	Method / Analyte / Units / LOR	ME-MS61 W ppm 0.1	ME-MS61 Y ppm 0.1	ME-MS61 Zn ppm 2	ME-MS61 Zr ppm 0.5	Ag-OG62 Ag ppm 1	Cu-OG62 Cu % 0.001	Ni-OG62 Ni % 0.001	CRU-QC Pass2mm % 0.01	PUL-QC Pass75um % 0.01
7623		0.8	33.0	16	146.0					
7624		0.7	31.8	9	99.1					
7625		<0.1	1.8	3	1.3					
7626		0.8	11.4	8	84.5					
7627		1.2	38.2	21	141.5					
7628		1.0	32.8	28	157.5					
7629		0.8	23.4	31	128.5					
7630		0.9	30.7	40	131.0					
7631		0.9	31.2	43	127.0					
7632		1.1	20.8	35	123.0					
7633		0.8	22.4	51	117.0					
7634		0.7	29.1	59	121.0					
7635		0.7	28.2	59	125.0					
7636		0.9	32.5	65	124.5					
7637		0.9	29.0	64	123.0					
7638		0.2	0.8	4	1.7					
7639		0.8	27.3	57	101.5					
7640		0.7	28.3	58	103.0					
7641		0.7	25.4	38	116.5					
7642		0.7	25.2	49	114.0					
7643		0.8	28.1	44	115.5					
7644		0.6	10.0	16	66.8					
7645		1.0	18.1	31	102.5					
7646		0.8	19.6	42	108.5					
7647		0.6	19.3	48	119.5					
7648		0.7	11.4	37	106.5					
7649		0.2	2.7	11	22.1					
7650		0.7	11.9	30	104.5					
7651		0.8	21.2	35	119.5					
7652		0.8	14.2	29	98.1					
7653		0.8	22.5	40	101.0					
7654		0.8	20.8	35	106.0					
7655		0.7	20.8	33	102.5					
7656		0.8	19.4	27	111.0					
7657		0.5	6.6	16	62.6					
7658		0.6	12.9	21	100.5					
7659		0.6	12.7	22	103.5					
7660		0.6	12.1	22	102.5					
7661		2.0	9.7	138	49.7		1.620	4.61		
7662		0.1	0.2	3	1.8				79.0	93.0

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 7-MAY-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18098245

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	ME-MS61 Ag ppm 0.01	ME-MS61 Al % 0.01	ME-MS61 As ppm 0.2	ME-MS61 Ba ppm 10	ME-MS61 Be ppm 0.05	ME-MS61 Bi ppm 0.01	ME-MS61 Ca % 0.01	ME-MS61 Cd ppm 0.02	ME-MS61 Ce ppm 0.01	ME-MS61 Co ppm 0.1	ME-MS61 Cr ppm 1	ME-MS61 Cs ppm 0.05	ME-MS61 Cu ppm 0.2	ME-MS61 Fe % 0.01
7663		1.25	0.02	1.30	0.4	10	0.53	0.16	0.12	<0.02	4.76	33.7	24	0.07	3.9	2.32
7664		1.17	0.02	6.71	0.9	100	1.55	0.25	0.37	<0.02	227	35.0	10	0.21	19.5	10.25
7665		2.02	0.02	4.26	1.1	50	0.93	0.25	0.26	<0.02	51.9	38.4	11	0.15	10.0	6.43
7666		1.95	0.02	4.78	1.0	60	0.95	0.21	0.34	<0.02	52.1	45.6	15	0.14	4.4	6.59
7667		2.02	0.01	0.32	0.2	10	0.40	0.05	0.02	<0.02	1.50	8.5	22	0.05	1.4	0.79
7668		1.82	0.02	0.54	0.7	10	0.38	0.17	0.02	<0.02	0.74	43.1	31	0.05	1.6	1.60
7669		2.14	0.02	1.06	7.7	10	0.44	0.53	0.03	<0.02	7.09	120.0	22	0.05	2.0	3.51
7670		2.05	0.01	0.33	0.2	10	0.32	0.05	0.02	<0.02	1.16	1.8	28	0.05	1.2	0.62
7671		2.09	0.01	2.75	0.5	40	0.93	0.10	0.10	<0.02	61.6	21.8	19	0.07	6.2	3.87
7672		1.92	0.01	0.79	<0.2	10	0.43	0.04	0.04	<0.02	40.5	8.5	38	0.06	1.1	1.50
7673		1.82	<0.01	0.17	<0.2	10	0.36	0.01	0.02	<0.02	0.39	0.6	34	0.06	1.1	0.47
7674		1.99	0.01	0.13	0.2	10	0.28	0.01	0.02	<0.02	0.66	1.0	27	0.06	1.2	0.43
7675		0.77	<0.01	0.05	0.2	10	0.05	0.01	31.9	<0.02	0.84	0.7	5	<0.05	1.5	0.12
7676		1.92	0.01	0.15	0.2	10	0.36	0.01	0.12	<0.02	1.04	1.0	34	0.07	1.3	0.39
7677		2.12	0.01	0.15	0.3	10	0.30	0.01	0.06	<0.02	0.58	2.0	31	0.06	1.1	0.44
7678		2.00	0.01	0.17	<0.2	10	0.38	0.01	0.02	<0.02	0.10	0.9	32	0.06	5.0	0.38
7679		1.93	0.02	0.16	0.5	10	0.42	0.01	0.02	0.02	0.17	0.6	34	0.06	36.8	0.32
7680		1.97	0.01	0.18	0.5	10	0.37	0.22	0.03	0.02	0.19	23.3	32	0.07	4.6	0.53
7681		1.98	0.01	0.18	0.4	10	0.42	0.01	0.02	0.02	0.09	0.5	29	0.07	11.2	0.36
7682		1.88	0.01	0.16	0.3	10	0.36	0.01	0.03	0.03	0.31	0.7	34	0.06	2.4	0.41
7683		2.03	0.01	0.19	0.5	10	0.33	0.01	0.03	0.02	0.24	0.9	29	0.06	5.1	0.35
7684		2.04	0.01	0.16	0.2	10	0.27	0.01	0.01	<0.02	0.04	0.7	29	0.05	1.9	0.42
7685		2.10	0.01	0.15	0.2	10	0.28	0.01	0.02	0.02	0.03	0.7	32	0.06	3.8	0.37
7686		2.14	0.01	0.16	0.2	10	0.34	0.03	0.02	0.02	0.10	4.4	33	0.07	1.9	0.38
7687		1.82	0.11	3.10	0.8	10	0.84	0.06	0.12	<0.02	12.75	14.2	29	0.06	4.9	2.36
7688		2.11	0.02	0.40	0.5	10	0.40	0.01	0.03	<0.02	0.22	1.7	32	0.06	1.7	0.63
7689		2.02	0.01	0.96	0.6	10	0.55	0.02	0.05	0.02	3.35	6.1	23	0.05	1.9	1.32
7690		2.12	0.01	1.96	0.5	10	0.61	0.01	0.11	0.02	4.14	3.0	29	<0.05	1.7	1.85
7691		2.24	0.02	2.90	0.6	20	0.72	0.05	0.15	<0.02	3.53	15.6	24	0.18	2.6	3.57
7692		2.24	0.01	3.88	0.7	40	0.92	0.04	0.20	<0.02	4.23	16.7	28	0.42	3.1	4.89
7693		1.79	0.01	3.47	0.5	40	0.83	0.02	0.27	0.02	5.58	11.4	21	0.37	3.8	4.17
7694		1.83	0.02	3.22	1.0	40	0.86	0.03	0.34	<0.02	4.34	12.6	25	0.40	2.9	3.96
7695		1.87	0.10	2.34	0.8	20	0.57	0.03	0.17	<0.02	9.99	11.3	22	0.20	2.6	2.88
7696		0.82	0.02	1.10	1.0	30	0.51	0.02	0.11	0.03	1.43	6.0	39	0.24	3.0	1.89
7697		0.99	0.02	3.51	1.7	50	0.79	0.02	0.22	0.03	5.16	19.8	25	0.54	6.7	3.81
7698		1.90	0.02	6.21	1.0	130	1.45	0.03	0.32	0.03	22.1	18.0	24	1.38	6.2	8.00
7699		0.77	0.01	4.88	1.0	120	1.19	0.02	0.29	0.02	10.10	14.8	21	1.32	4.2	6.01
7700		1.01	0.02	4.13	0.9	90	1.05	0.02	0.28	0.03	7.80	13.5	19	1.05	5.5	5.18
7701		0.07	>100	4.07	1920	120	0.70	156.5	0.32	57.2	28.4	16.1	44	1.70	>10000	2.86
7702		1.61	0.20	5.17	2.0	120	1.22	0.11	0.32	0.05	10.80	23.9	24	1.28	18.4	7.08

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 7-MAY-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18098245

Sample Description	Method / Analyte / Units / LOR	ME-MS61 Ga ppm 0.05	ME-MS61 Ge ppm 0.05	ME-MS61 Hf ppm 0.1	ME-MS61 In ppm 0.005	ME-MS61 K % 0.01	ME-MS61 La ppm 0.5	ME-MS61 Li ppm 0.2	ME-MS61 Mg % 0.01	ME-MS61 Mn ppm 5	ME-MS61 Mo ppm 0.05	ME-MS61 Na % 0.01	ME-MS61 Nb ppm 0.1	ME-MS61 Ni ppm 0.2	ME-MS61 P ppm 10	ME-MS61 Pb ppm 0.5
7663		7.19	0.05	0.5	0.008	0.07	2.4	5.0	0.49	61	8.43	0.64	0.9	17.3	110	2.1
7664		28.3	0.24	2.3	0.034	0.59	128.5	18.6	1.45	139	2.87	3.56	2.2	50.8	420	2.5
7665		18.05	0.11	1.6	0.017	0.34	28.6	13.0	1.15	129	7.66	2.23	1.9	30.9	310	2.4
7666		19.90	0.11	1.9	0.019	0.36	29.3	11.9	1.08	106	5.11	2.66	2.3	31.7	360	2.9
7667		2.66	<0.05	<0.1	<0.005	0.04	0.8	1.8	0.18	52	2.74	0.08	0.1	8.6	10	0.9
7668		3.62	<0.05	0.1	0.005	0.04	<0.5	4.5	0.25	59	13.50	0.20	0.1	11.0	20	1.0
7669		9.07	0.05	0.1	0.008	0.04	3.4	10.0	0.72	75	10.85	0.27	0.1	29.5	20	1.2
7670		1.39	<0.05	0.1	<0.005	0.03	0.6	1.5	0.07	49	5.89	0.18	0.1	3.6	10	0.8
7671		12.45	0.10	1.1	0.011	0.20	33.0	12.7	0.69	79	2.91	1.39	0.9	32.6	220	1.4
7672		3.80	0.07	0.3	<0.005	0.05	20.8	3.5	0.16	51	3.98	0.46	0.4	6.7	60	1.2
7673		0.72	<0.05	<0.1	<0.005	0.03	<0.5	1.3	0.04	45	1.97	0.07	<0.1	2.3	<10	1.0
7674		1.29	<0.05	<0.1	<0.005	0.03	<0.5	1.0	0.03	44	1.56	0.05	<0.1	2.1	<10	0.9
7675		0.22	0.06	<0.1	<0.005	<0.01	1.0	1.1	1.49	76	0.31	0.02	0.1	0.8	60	<0.5
7676		0.82	<0.05	<0.1	<0.005	0.03	0.6	1.1	0.03	40	1.97	0.06	<0.1	2.1	<10	1.0
7677		0.60	<0.05	<0.1	<0.005	0.03	<0.5	1.2	0.04	43	1.84	0.06	<0.1	2.3	<10	0.9
7678		0.59	<0.05	<0.1	<0.005	0.03	<0.5	1.1	0.03	39	1.90	0.08	<0.1	3.0	<10	1.4
7679		0.53	<0.05	<0.1	<0.005	0.04	<0.5	0.8	0.02	32	1.97	0.08	<0.1	8.0	<10	1.5
7680		0.55	<0.05	<0.1	<0.005	0.04	<0.5	0.8	0.03	44	1.98	0.08	<0.1	4.2	<10	3.0
7681		0.61	<0.05	<0.1	<0.005	0.04	<0.5	0.9	0.04	34	1.70	0.07	<0.1	7.5	<10	1.7
7682		0.58	<0.05	<0.1	<0.005	0.04	<0.5	0.9	0.03	44	2.04	0.06	<0.1	2.4	<10	1.8
7683		0.70	<0.05	<0.1	<0.005	0.04	<0.5	0.9	0.04	35	1.67	0.08	<0.1	2.6	<10	2.0
7684		0.65	<0.05	<0.1	<0.005	0.04	<0.5	0.9	0.04	44	1.59	0.05	<0.1	2.4	<10	1.9
7685		0.64	<0.05	<0.1	<0.005	0.03	<0.5	0.9	0.04	37	1.71	0.06	<0.1	2.5	<10	3.4
7686		0.49	<0.05	<0.1	<0.005	0.03	<0.5	0.8	0.03	39	1.96	0.08	<0.1	2.0	<10	3.1
7687		11.65	0.05	0.8	0.005	0.07	6.5	5.1	0.55	65	3.41	2.02	1.3	16.5	200	3.8
7688		2.06	<0.05	<0.1	<0.005	0.04	<0.5	1.5	0.15	47	1.92	0.17	0.1	5.3	20	2.4
7689		5.43	<0.05	0.2	<0.005	0.04	1.8	2.5	0.36	49	1.39	0.46	0.5	11.9	50	2.9
7690		10.40	<0.05	0.5	0.005	0.06	2.1	3.8	0.64	70	3.21	1.07	1.3	19.5	160	3.3
7691		19.75	<0.05	0.8	0.012	0.12	1.8	8.2	1.41	143	9.33	1.23	1.7	42.3	170	2.6
7692		28.6	0.05	1.0	0.020	0.29	2.0	14.5	2.40	214	1.62	1.29	2.4	66.1	230	2.1
7693		23.5	0.05	1.0	0.013	0.26	2.9	12.3	2.03	194	2.39	1.23	2.1	52.8	210	2.7
7694		21.4	<0.05	0.8	0.010	0.28	2.2	11.0	1.77	183	2.45	1.18	2.1	48.9	190	3.0
7695		13.60	<0.05	0.6	0.007	0.12	5.4	6.6	1.04	134	1.87	1.06	1.3	29.7	130	3.2
7696		10.50	<0.05	0.2	0.005	0.16	0.7	4.9	0.95	119	3.53	0.16	0.8	27.0	70	5.2
7697		23.9	0.05	0.8	0.012	0.39	2.5	11.9	1.96	234	1.29	1.27	2.5	55.6	220	8.6
7698		38.9	0.08	1.7	0.022	1.00	12.2	25.0	3.50	524	1.16	2.18	3.7	92.4	350	6.3
7699		29.0	0.07	1.4	0.014	0.88	5.2	14.9	2.41	421	1.15	1.86	3.0	60.5	280	7.0
7700		25.2	0.06	1.1	0.012	0.69	4.0	13.5	2.18	382	1.04	1.46	2.4	57.5	240	6.9
7701		24.5	0.22	2.7	12.05	0.61	13.8	18.2	0.08	146	6.58	0.41	7.9	116.0	540	2040
7702		27.1	0.08	1.4	0.020	0.83	5.4	13.7	2.34	463	1.14	2.04	2.7	66.7	270	5.5

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 7-MAY-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18098245

Sample Description	Method / Analyte / Units / LOR	ME-MS61 Rb ppm 0.1	ME-MS61 Re ppm 0.002	ME-MS61 S % 0.01	ME-MS61 Sb ppm 0.05	ME-MS61 Sc ppm 0.1	ME-MS61 Se ppm 1	ME-MS61 Sn ppm 0.2	ME-MS61 Sr ppm 0.2	ME-MS61 Ta ppm 0.05	ME-MS61 Te ppm 0.05	ME-MS61 Th ppm 0.01	ME-MS61 Ti % 0.005	ME-MS61 Tl ppm 0.02	ME-MS61 U ppm 0.1	ME-MS61 V ppm 1
7663		2.8	0.002	0.25	0.49	4.7	<1	1.0	10.1	0.06	<0.05	0.68	0.177	0.02	2.2	104
7664		27.6	<0.002	0.27	0.25	23.5	1	1.4	61.5	0.18	<0.05	3.04	0.622	0.08	2.0	521
7665		15.2	<0.002	0.27	0.30	16.8	1	1.4	31.9	0.15	<0.05	2.07	0.349	0.05	2.0	185
7666		15.3	<0.002	0.30	0.31	17.3	1	1.5	32.0	0.18	<0.05	2.42	0.386	0.05	2.0	188
7667		0.9	<0.002	0.05	0.55	0.8	1	<0.2	4.6	<0.05	<0.05	0.04	0.010	0.02	0.2	15
7668		1.2	0.002	0.26	0.45	1.5	1	0.5	5.0	<0.05	<0.05	0.11	0.014	0.02	0.7	34
7669		1.3	<0.002	1.39	0.56	3.6	2	0.6	5.2	<0.05	0.06	0.16	0.016	<0.02	2.0	54
7670		1.0	<0.002	0.01	0.45	0.5	<1	<0.2	4.7	<0.05	<0.05	0.10	0.009	<0.02	0.2	7
7671		9.5	<0.002	0.15	0.48	9.9	1	0.7	17.9	0.07	<0.05	1.41	0.123	0.04	1.3	115
7672		2.2	<0.002	0.06	0.41	2.5	<1	0.4	8.0	<0.05	<0.05	0.39	0.047	0.02	0.4	44
7673		1.2	<0.002	<0.01	0.54	0.2	<1	<0.2	5.0	<0.05	<0.05	0.01	<0.005	<0.02	<0.1	3
7674		1.1	<0.002	0.01	0.50	0.1	<1	<0.2	4.3	<0.05	<0.05	<0.01	<0.005	<0.02	<0.1	1
7675		0.1	<0.002	<0.01	0.07	0.2	1	<0.2	77.0	<0.05	<0.05	0.05	<0.005	<0.02	0.1	1
7676		1.3	<0.002	0.01	0.53	0.1	<1	<0.2	5.2	<0.05	<0.05	<0.01	<0.005	0.02	<0.1	2
7677		1.1	<0.002	0.02	0.49	0.2	<1	<0.2	4.8	<0.05	<0.05	<0.01	<0.005	0.02	<0.1	2
7678		1.2	<0.002	0.01	0.58	0.1	1	<0.2	4.9	<0.05	<0.05	<0.01	<0.005	0.02	<0.1	1
7679		1.3	<0.002	0.01	0.58	0.1	<1	<0.2	4.9	<0.05	<0.05	0.01	<0.005	0.02	<0.1	1
7680		1.1	<0.002	0.15	0.51	0.2	1	<0.2	5.8	<0.05	<0.05	0.01	<0.005	0.02	<0.1	2
7681		1.2	<0.002	<0.01	0.61	0.2	<1	<0.2	5.5	<0.05	<0.05	<0.01	<0.005	0.02	<0.1	2
7682		1.3	<0.002	<0.01	0.56	0.2	<1	<0.2	5.3	<0.05	<0.05	<0.01	<0.005	0.02	<0.1	2
7683		1.5	<0.002	0.01	0.46	0.2	<1	<0.2	5.7	<0.05	<0.05	0.01	<0.005	0.02	<0.1	2
7684		1.2	<0.002	<0.01	0.35	0.2	<1	<0.2	4.2	<0.05	<0.05	<0.01	<0.005	<0.02	<0.1	2
7685		1.1	<0.002	<0.01	0.37	0.2	<1	<0.2	5.4	<0.05	<0.05	<0.01	<0.005	<0.02	<0.1	2
7686		1.1	<0.002	0.03	0.43	0.2	<1	<0.2	5.3	<0.05	<0.05	0.01	<0.005	0.02	<0.1	2
7687		2.0	<0.002	0.10	0.44	6.0	<1	1.1	13.5	0.06	<0.05	0.87	0.120	0.02	1.1	64
7688		1.0	<0.002	0.01	0.56	0.9	<1	<0.2	5.0	<0.05	<0.05	0.05	0.009	<0.02	0.1	7
7689		0.9	<0.002	0.05	0.56	1.8	1	0.3	5.5	<0.05	<0.05	0.25	0.052	<0.02	0.4	31
7690		1.1	<0.002	0.01	0.43	3.4	<1	0.3	5.5	0.05	<0.05	0.54	0.103	<0.02	0.8	46
7691		4.5	<0.002	0.11	0.36	10.3	<1	0.8	5.4	0.10	<0.05	0.86	0.206	0.02	1.1	99
7692		13.2	<0.002	0.09	0.35	15.4	<1	1.1	5.3	0.12	<0.05	1.12	0.271	0.06	1.6	123
7693		11.2	<0.002	0.03	0.42	13.9	<1	1.3	6.1	0.11	<0.05	1.05	0.250	0.06	1.4	105
7694		12.9	<0.002	0.07	0.44	12.1	<1	1.0	6.6	0.10	<0.05	0.93	0.218	0.07	1.5	98
7695		4.9	<0.002	0.08	0.40	7.6	<1	0.8	5.2	0.07	<0.05	0.71	0.167	0.03	0.8	72
7696		6.8	<0.002	0.03	0.52	4.0	<1	0.3	3.9	<0.05	<0.05	0.24	0.047	0.04	0.7	40
7697		18.2	<0.002	0.11	0.42	11.2	<1	1.1	5.4	0.11	<0.05	0.92	0.235	0.09	1.2	91
7698		49.1	<0.002	0.10	0.27	26.6	<1	1.6	10.1	0.22	<0.05	1.95	0.489	0.23	2.0	218
7699		44.5	<0.002	0.02	0.32	17.3	<1	1.1	10.3	0.16	<0.05	1.54	0.369	0.21	1.7	172
7700		34.4	<0.002	0.03	0.31	15.3	<1	0.9	9.9	0.13	<0.05	1.22	0.295	0.16	1.4	148
7701		24.0	0.002	3.81	219	4.1	66	12.8	521	0.57	61.4	5.94	0.205	4.12	2.7	33
7702		43.8	<0.002	0.10	0.37	21.1	<1	1.0	14.2	0.16	<0.05	1.57	0.378	0.20	1.3	193

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 7-MAY-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18098245

Sample Description	Method / Analyte / Units / LOR	ME-MS61 W ppm 0.1	ME-MS61 Y ppm 0.1	ME-MS61 Zn ppm 2	ME-MS61 Zr ppm 0.5	Ag-OG62 Ag ppm 1	Cu-OG62 Cu % 0.001	Ni-OG62 Ni % 0.001	CRU-QC Pass2mm % 0.01	PUL-QC Pass75um % 0.01
7663		0.6	2.4	6	20.3					
7664		0.5	12.3	15	84.5					
7665		0.6	5.7	12	61.5					
7666		0.8	6.7	12	71.2					
7667		0.1	0.1	3	1.2					
7668		0.3	0.3	3	4.2					
7669		0.4	0.4	6	3.0					
7670		0.1	0.2	2	2.5					
7671		0.5	3.6	8	41.3					
7672		0.2	1.2	3	10.1					
7673		<0.1	<0.1	2	<0.5					
7674		<0.1	<0.1	2	<0.5					
7675		<0.1	1.7	2	1.1					
7676		0.1	0.1	2	<0.5					
7677		0.1	<0.1	2	<0.5					
7678		<0.1	<0.1	3	<0.5					93.7
7679		0.1	<0.1	3	<0.5					94.1
7680		<0.1	<0.1	5	<0.5					
7681		0.1	<0.1	4	<0.5					
7682		0.1	<0.1	4	<0.5					
7683		0.1	<0.1	5	<0.5					
7684		0.1	<0.1	4	<0.5					
7685		0.1	<0.1	5	<0.5					
7686		<0.1	<0.1	8	<0.5					
7687		1.0	3.8	10	30.1					
7688		0.1	0.1	6	1.8					
7689		0.3	0.6	10	7.9					
7690		0.3	1.9	13	18.0					
7691		0.3	3.3	24	28.4					
7692		0.4	4.6	40	38.6					
7693		0.3	7.0	36	36.7					
7694		0.3	3.1	35	30.8					
7695		0.5	2.4	23	23.4					
7696		0.2	0.9	22	7.4					
7697		0.3	3.8	46	32.9					
7698		0.5	10.3	84	65.3					
7699		0.4	8.4	64	49.1					
7700		0.3	7.1	59	39.9					
7701		15.3	5.8	9330	89.5	310	1.025			
7702		0.3	9.5	71	52.1				78.4	85.1

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 7-MAY-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18098245

Sample Description	Method	WEI-21	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61
	Analyte	Recvd Wt.	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe
	Units	kg	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	%
	LOR	0.02	0.01	0.01	0.2	10	0.05	0.01	0.01	0.02	0.01	0.1	1	0.05	0.2	0.01
7703		1.54	0.03	2.89	0.8	40	0.59	0.02	0.36	0.02	3.82	12.3	30	0.43	3.8	3.36
7704		1.56	0.05	7.22	1.3	190	1.53	0.27	4.84	0.03	19.25	37.1	24	1.04	79.1	7.76
7705		1.61	0.09	7.83	1.3	120	0.87	0.24	5.68	0.04	21.3	43.7	20	0.64	199.0	8.29
7706		1.14	0.06	7.75	1.5	180	0.81	0.26	5.54	0.03	20.6	43.7	18	0.90	120.0	8.42
7707		2.09	0.04	7.69	1.1	160	1.14	0.21	5.08	0.03	20.7	39.4	19	0.95	95.3	8.49
7708		1.40	0.03	7.88	1.3	140	0.93	0.09	3.53	0.02	23.0	45.5	21	0.93	56.3	8.99

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 7-MAY-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18098245

Sample Description	Method / Analyte / Units / LOR	ME-MS61 Ga ppm 0.05	ME-MS61 Ge ppm 0.05	ME-MS61 Hf ppm 0.1	ME-MS61 In ppm 0.005	ME-MS61 K % 0.01	ME-MS61 La ppm 0.5	ME-MS61 Li ppm 0.2	ME-MS61 Mg % 0.01	ME-MS61 Mn ppm 5	ME-MS61 Mo ppm 0.05	ME-MS61 Na % 0.01	ME-MS61 Nb ppm 0.1	ME-MS61 Ni ppm 0.2	ME-MS61 P ppm 10	ME-MS61 Pb ppm 0.5
7703		16.60	0.05	0.7	0.012	0.29	1.7	8.4	1.49	306	4.55	1.01	2.0	35.7	180	3.4
7704		19.50	0.10	1.6	0.074	1.05	9.3	14.7	2.93	870	1.62	1.95	3.5	64.4	350	4.5
7705		18.80	0.10	1.7	0.066	0.65	10.2	14.3	3.26	1060	0.64	2.35	3.7	69.1	380	4.6
7706		18.75	0.09	1.8	0.065	0.95	9.7	15.5	3.33	1120	0.57	2.27	3.7	70.2	380	4.9
7707		20.6	0.10	1.8	0.073	0.84	10.0	14.5	3.24	1140	0.58	2.28	3.7	68.5	390	4.1
7708		26.9	0.08	1.9	0.059	0.69	12.3	17.0	3.52	1050	1.39	2.47	3.7	80.2	400	3.5

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 7-MAY-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18098245

Sample Description	Method / Analyte / Units / LOR	ME-MS61 Rb ppm 0.1	ME-MS61 Re ppm 0.002	ME-MS61 S % 0.01	ME-MS61 Sb ppm 0.05	ME-MS61 Sc ppm 0.1	ME-MS61 Se ppm 1	ME-MS61 Sn ppm 0.2	ME-MS61 Sr ppm 0.2	ME-MS61 Ta ppm 0.05	ME-MS61 Te ppm 0.05	ME-MS61 Th ppm 0.01	ME-MS61 Ti % 0.005	ME-MS61 Tl ppm 0.02	ME-MS61 U ppm 0.1	ME-MS61 V ppm 1
7703		14.2	<0.002	0.02	0.42	10.2	<1	0.9	10.2	0.09	<0.05	0.84	0.201	0.07	1.0	83
7704		51.2	0.002	0.11	0.49	28.8	<1	1.2	203	0.24	<0.05	2.18	0.504	0.23	0.9	227
7705		32.7	<0.002	0.08	0.41	31.7	1	0.8	194.0	0.26	<0.05	2.32	0.545	0.15	0.7	240
7706		47.1	<0.002	0.09	0.39	32.3	1	0.9	183.5	0.25	<0.05	2.39	0.543	0.20	0.7	244
7707		42.9	0.002	0.09	0.30	31.7	1	1.0	155.5	0.25	<0.05	2.34	0.528	0.18	0.8	236
7708		34.1	<0.002	0.14	0.22	31.8	1	1.0	85.3	0.24	<0.05	2.26	0.536	0.16	1.4	262

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 7-MAY-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18098245

Sample Description	Method Analyte Units LOR	ME-MS61 W ppm 0.1	ME-MS61 Y ppm 0.1	ME-MS61 Zn ppm 2	ME-MS61 Zr ppm 0.5	Ag-OG62 Ag ppm 1	Cu-OG62 Cu % 0.001	Ni-OG62 Ni % 0.001	CRU-QC Pass2mm % 0.01	PUL-QC Pass75um % 0.01
7703		0.2	6.5	42	27.5					
7704		0.5	15.7	75	57.7					
7705		0.6	18.4	87	64.7					
7706		0.5	17.5	91	66.8					
7707		0.5	17.4	93	65.9					
7708		0.7	12.9	109	70.3					

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 7-MAY-2018
Account: BMRPLLBW

Project: Iron Mask

CERTIFICATE OF ANALYSIS SD18098245

CERTIFICATE COMMENTS

ANALYTICAL COMMENTS

Applies to Method: REE's may not be totally soluble in this method.
ME-MS61

LABORATORY ADDRESSES

Applies to Method: Processed at ALS Sudbury located at 1351-B Kelly Lake Road, Unit #1, Sudbury, ON, Canada.

CRU-31	CRU-QC	LOG-22	LOG-24
PUL-31	PUL-QC	SPL-21	WEI-21

Applies to Method: Processed at ALS Vancouver located at 2103 Dollarton Hwy, North Vancouver, BC, Canada.

Ag-OG62	Cu-OG62	ME-MS61	ME-OG62
Ni-OG62			