ALS Canada Ltd.

2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 5-JUN-2018
Account: BMRPLLBW

CERTIFICATE SD18114878

Project: IRON MASK

This report is for 173 Drill Core samples submitted to our lab in Sudbury, ON, Canada on 17-MAY-2018.

The following have access to data associated with this certificate:

SANDY DE LA MARE	PETER DOYLE	JON EDWARDS
MIKE HENDRICKSON	FRANK PLOEGER	IAN PRINGLE
MERCEDES RICH	CLYDE SMITH	

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
LOG-24	Pulp Login - Rcd w/o Barcode
CRU-31	Fine crushing - 70% <2mm
CRU-QC	Crushing QC Test
PUL-QC	Pulverizing QC Test
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
ME-OG62	Ore Grade Elements - Four Acid	ICP-AES
Cu-OG62	Ore Grade Cu - Four Acid	ICP-AES
Ni-OG62	Ore Grade Ni - Four Acid	ICP-AES
ME-MS61	48 element four acid ICP-MS	
Ag-OG62	Ore Grade Ag - Four Acid	ICP-AES

To: **BATTERY MINERAL RESOURCES LTD.**
ATTN: PETER DOYLE
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

***** See Appendix Page for comments regarding this certificate *****

Signature:
Colin Ramshaw, Vancouver Laboratory Manager

ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: BATTERY MINERAL RESOURCES LTD.
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 5-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18114878

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	ME-MS61 Ag ppm 0.01	ME-MS61 Al % 0.01	ME-MS61 As ppm 0.2	ME-MS61 Ba ppm 10	ME-MS61 Be ppm 0.05	ME-MS61 Bi ppm 0.01	ME-MS61 Ca % 0.01	ME-MS61 Cd ppm 0.02	ME-MS61 Ce ppm 0.01	ME-MS61 Co ppm 0.1	ME-MS61 Cr ppm 1	ME-MS61 Cs ppm 0.05	ME-MS61 Cu ppm 0.2	ME-MS61 Fe % 0.01
8345		1.94	0.08	7.09	22.0	220	1.08	0.29	0.27	0.02	43.2	19.8	84	0.75	3.1	3.20
8346		2.02	0.01	7.98	8.2	640	3.05	0.23	0.37	<0.02	55.1	16.1	117	2.46	2.1	4.56
8347		1.90	<0.01	6.49	7.3	80	1.19	0.11	0.61	<0.02	18.60	7.7	80	0.25	1.6	3.06
8348		2.04	0.02	6.85	5.0	140	1.32	0.15	0.26	<0.02	55.3	21.3	74	0.35	2.0	3.94
8349		2.13	0.01	7.25	1.7	500	1.79	0.13	0.42	<0.02	59.7	10.4	88	1.29	1.9	4.06
8350		2.05	0.04	6.98	3.2	210	1.15	0.33	0.90	<0.02	50.0	17.0	83	1.07	24.6	3.34
8351		2.30	0.08	8.14	1.8	880	1.99	0.42	0.72	0.06	55.1	15.9	130	3.52	27.6	4.09
8352		1.92	0.13	8.36	5.6	830	2.95	0.31	0.51	<0.02	59.1	22.6	122	3.26	139.0	4.16
8353		2.49	0.18	7.34	1.0	440	2.07	0.14	0.36	<0.02	46.0	11.6	102	2.05	155.5	3.93
8354		2.00	0.01	6.09	3.4	160	1.39	0.15	1.09	<0.02	26.3	54.7	63	0.68	4.7	2.70
8355		2.09	0.01	6.78	0.7	200	0.96	0.06	0.33	<0.02	38.3	22.0	79	0.90	4.3	3.52
8356		2.04	0.02	6.17	2.3	190	1.03	0.13	0.20	<0.02	43.2	41.1	57	1.01	2.0	3.21
8357		2.06	0.01	5.26	7.2	110	0.98	0.38	0.68	<0.02	14.80	91.9	36	0.54	2.6	2.46
8358		2.01	0.02	5.95	4.6	150	1.08	0.26	0.23	<0.02	20.9	66.2	51	0.87	2.4	2.62
8359		0.88	0.01	7.31	1.8	690	2.40	0.22	0.45	<0.02	42.2	31.7	110	2.11	2.8	3.56
8360		1.01	0.02	7.68	2.6	740	2.96	0.28	0.48	<0.02	52.6	33.5	118	2.42	3.5	3.78
8361		0.08	3.78	5.53	12.8	120	0.51	0.77	3.44	2.04	15.70	973	266	0.76	>10000	18.05
8362		2.09	0.03	7.05	0.9	340	1.56	0.20	0.27	<0.02	41.6	13.1	88	0.49	41.8	3.26
8363		2.02	0.02	5.58	3.7	140	0.84	0.20	0.84	<0.02	31.5	74.8	42	0.46	17.4	2.43
8364		1.89	0.01	5.54	3.8	120	0.68	0.12	0.34	<0.02	13.75	61.4	42	0.47	4.9	1.98
8365		2.04	0.02	5.92	8.9	150	1.01	0.30	0.20	<0.02	30.3	127.5	54	0.62	7.8	3.10
8366		2.04	0.02	7.72	2.0	270	1.94	0.27	0.45	0.09	55.0	15.1	129	1.02	2.1	4.04
8367		2.12	0.02	7.39	1.3	290	1.82	0.15	0.40	<0.02	43.9	20.4	122	0.65	3.2	4.00
8368		2.00	0.02	7.11	2.2	130	1.48	0.15	0.35	<0.02	43.7	21.8	134	0.44	14.1	3.78
8369		1.99	0.01	7.45	1.2	410	2.04	0.17	0.35	<0.02	50.5	17.4	114	0.83	4.9	3.82
8370		1.83	0.02	7.15	3.5	280	1.62	0.15	0.29	<0.02	45.9	18.6	108	0.42	23.1	3.65
8371		2.07	0.02	7.16	2.8	170	1.46	0.42	0.24	<0.02	43.0	34.9	107	0.35	48.1	4.04
8372		2.06	0.03	7.27	8.6	60	1.54	0.74	0.23	<0.02	43.3	88.0	106	0.22	145.0	4.22
8373		2.58	0.03	7.37	3.0	40	1.66	0.47	0.29	<0.02	45.4	43.3	108	0.16	353	4.07
8374		2.13	0.02	7.30	9.7	120	1.51	0.41	0.28	<0.02	40.1	87.7	116	0.42	128.0	4.71
8375		1.01	<0.01	0.07	<0.2	10	<0.05	0.02	33.3	<0.02	0.98	0.6	3	<0.05	3.1	0.13
8376		2.15	0.02	7.66	2.3	280	1.89	0.25	0.48	<0.02	45.0	32.8	134	0.99	220	4.91
8377		2.03	0.01	7.15	2.3	100	1.11	0.30	0.40	<0.02	44.2	26.8	94	0.33	55.9	3.61
8378		1.46	0.01	7.62	1.1	270	1.58	0.20	0.31	<0.02	58.3	17.3	108	0.51	5.9	4.08
8379		1.36	0.01	6.85	2.6	180	1.25	0.29	0.27	<0.02	34.2	47.8	74	0.19	5.2	3.19
8380		2.21	0.02	4.46	34.0	50	0.70	0.97	0.38	<0.02	39.7	492	47	0.35	24.1	11.10
8381		1.51	0.02	5.89	2.9	40	4.30	0.67	0.33	<0.02	37.7	134.0	85	0.25	23.7	9.78
8382		2.11	0.03	6.82	2.5	50	10.40	0.64	0.27	<0.02	29.0	93.3	101	0.10	9.6	6.18
8383		2.12	0.02	7.64	1.5	80	2.13	0.21	0.32	<0.02	45.1	37.3	112	0.15	4.2	5.54
8384		2.20	0.01	7.61	3.0	150	1.76	0.23	0.34	<0.02	60.8	27.0	113	0.25	4.7	3.84

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: BATTERY MINERAL RESOURCES LTD.
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 5-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18114878

Sample Description	Method / Analyte / Units / LOR	ME-MS61 Ga ppm 0.05	ME-MS61 Ge ppm 0.05	ME-MS61 Hf ppm 0.1	ME-MS61 In ppm 0.005	ME-MS61 K % 0.01	ME-MS61 La ppm 0.5	ME-MS61 Li ppm 0.2	ME-MS61 Mg % 0.01	ME-MS61 Mn ppm 5	ME-MS61 Mo ppm 0.05	ME-MS61 Na % 0.01	ME-MS61 Nb ppm 0.1	ME-MS61 Ni ppm 0.2	ME-MS61 P ppm 10	ME-MS61 Pb ppm 0.5
8345		16.25	0.09	2.7	0.015	0.90	19.2	9.8	1.47	172	1.01	3.85	4.9	37.1	470	4.3
8346		21.0	0.11	3.3	0.068	2.37	26.3	16.7	2.30	230	0.95	2.59	6.9	58.1	590	4.2
8347		13.75	0.08	2.6	0.011	0.42	8.6	8.6	1.23	191	0.83	4.01	4.5	27.9	350	3.6
8348		15.70	0.10	2.8	0.014	0.61	25.9	10.3	1.54	189	1.11	3.75	5.2	30.8	400	3.5
8349		18.10	0.12	2.7	0.034	1.31	27.6	14.6	2.10	275	1.02	3.15	5.1	40.7	460	4.1
8350		15.40	0.10	2.9	0.027	0.89	23.5	13.2	1.73	492	1.01	3.73	4.8	39.9	420	6.0
8351		20.7	0.09	4.1	0.065	2.75	26.4	15.2	2.29	550	2.14	2.14	6.9	58.9	530	12.5
8352		23.8	0.11	3.4	0.067	2.90	29.0	19.7	2.12	442	2.48	2.43	8.7	66.9	490	4.3
8353		20.5	0.11	3.7	0.035	1.78	23.2	15.8	1.83	425	1.74	3.01	6.3	46.6	430	3.6
8354		13.50	0.07	2.8	0.019	0.86	11.9	7.3	0.89	243	1.20	3.59	4.4	20.2	320	4.2
8355		16.35	0.09	3.6	0.018	1.07	18.3	9.5	1.26	204	1.18	3.74	5.5	25.9	430	3.0
8356		14.45	0.10	2.5	0.014	1.08	21.0	8.3	1.02	162	1.06	3.43	4.4	20.7	300	3.8
8357		10.00	0.07	1.3	0.010	0.71	7.2	4.6	0.57	136	1.08	3.21	2.1	21.1	170	5.2
8358		12.20	0.05	2.0	0.011	0.91	9.5	6.3	0.75	128	0.97	3.61	3.5	13.3	250	3.8
8359		20.3	0.08	3.4	0.047	2.33	20.7	13.8	1.66	191	1.32	2.54	5.9	37.8	450	3.5
8360		22.4	0.11	3.9	0.048	2.49	25.8	15.5	1.76	200	1.54	2.55	6.7	42.5	480	3.7
8361		11.50	0.20	1.2	0.121	0.32	7.1	7.9	4.04	1020	4.43	1.19	4.5	>10000	460	13.2
8362		17.15	0.09	3.5	0.025	1.42	20.7	9.0	1.40	171	1.15	3.32	5.6	43.3	400	2.6
8363		11.65	0.06	1.4	0.012	0.72	14.8	4.8	0.73	163	1.02	3.35	2.7	21.0	220	4.2
8364		11.35	0.05	1.6	0.009	0.72	6.7	4.7	0.67	114	1.02	3.42	2.8	11.6	200	3.5
8365		13.95	0.06	1.8	0.012	0.75	14.5	7.6	1.09	152	1.40	3.32	3.2	21.6	270	3.3
8366		20.8	0.10	4.5	0.027	1.01	27.5	14.8	2.26	219	1.83	3.68	7.1	49.7	520	6.0
8367		18.65	0.07	4.2	0.020	0.89	21.6	15.3	2.33	221	1.51	3.30	5.7	50.6	470	7.2
8368		18.05	0.09	4.5	0.018	0.51	21.8	13.9	2.15	206	1.40	3.70	5.1	49.3	430	4.9
8369		18.60	0.09	4.1	0.029	1.23	24.7	14.3	2.20	189	1.37	3.09	4.5	45.4	470	6.4
8370		17.80	0.08	3.8	0.024	0.88	22.9	12.8	1.99	170	1.98	3.29	4.6	47.4	430	2.7
8371		17.70	0.09	3.9	0.019	0.57	21.1	12.2	1.91	188	1.48	3.58	5.5	42.7	430	2.5
8372		16.65	0.08	4.0	0.019	0.29	21.3	10.0	1.73	195	1.42	4.16	5.3	36.9	430	1.9
8373		16.85	0.08	4.4	0.022	0.32	22.3	10.4	1.70	193	1.31	4.31	5.9	38.6	490	1.9
8374		18.05	0.06	4.2	0.021	0.50	19.7	13.0	2.06	218	1.21	3.67	5.7	44.8	440	2.1
8375		0.22	0.07	0.1	0.006	0.01	1.1	<0.2	1.19	87	0.16	0.03	0.1	0.5	60	<0.5
8376		19.45	0.08	4.1	0.034	1.18	21.6	15.7	2.49	245	1.23	3.21	5.6	56.2	500	2.3
8377		15.80	0.08	4.4	0.018	0.48	22.0	7.9	1.53	176	1.41	4.11	6.0	30.1	450	2.2
8378		18.05	0.10	4.8	0.027	0.91	28.0	10.2	1.85	183	1.82	3.73	6.9	36.2	490	2.7
8379		15.40	0.06	3.4	0.017	0.88	15.9	6.3	1.18	151	1.63	3.81	5.0	23.5	350	2.6
8380		12.25	0.06	1.6	0.013	0.47	19.7	2.4	0.57	109	1.31	2.89	2.9	17.7	200	3.5
8381		12.35	0.07	3.2	0.017	0.57	17.4	2.6	0.72	122	4.36	4.00	3.3	18.3	330	2.7
8382		14.80	0.10	4.7	0.010	0.68	11.9	4.5	1.04	112	4.14	4.25	5.2	25.8	430	2.4
8383		17.80	0.06	4.8	0.017	0.49	22.1	8.6	1.73	161	5.41	4.27	6.4	37.4	480	2.6
8384		18.35	0.10	4.9	0.021	0.63	29.5	9.5	1.77	163	1.51	4.11	7.0	37.9	490	2.6

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: BATTERY MINERAL RESOURCES LTD.
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 5-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18114878

Sample Description	Method / Analyte / Units / LOR	ME-MS61 Rb ppm 0.1	ME-MS61 Re ppm 0.002	ME-MS61 S % 0.01	ME-MS61 Sb ppm 0.05	ME-MS61 Sc ppm 0.1	ME-MS61 Se ppm 1	ME-MS61 Sn ppm 0.2	ME-MS61 Sr ppm 0.2	ME-MS61 Ta ppm 0.05	ME-MS61 Te ppm 0.05	ME-MS61 Th ppm 0.01	ME-MS61 Ti % 0.005	ME-MS61 Tl ppm 0.02	ME-MS61 U ppm 0.1	ME-MS61 V ppm 1
8345		34.6	<0.002	0.04	0.17	9.8	<1	0.9	96.3	0.46	<0.05	5.72	0.246	0.25	1.9	69
8346		102.0	<0.002	0.04	0.20	13.1	<1	1.3	109.5	0.64	<0.05	7.36	0.353	0.59	3.0	106
8347		15.2	<0.002	0.03	0.13	7.5	<1	0.8	74.1	0.45	<0.05	6.35	0.206	0.10	1.7	58
8348		20.9	<0.002	0.16	0.16	9.1	<1	0.9	79.0	0.53	<0.05	5.74	0.252	0.13	1.9	70
8349		51.8	<0.002	0.05	0.16	11.4	<1	1.0	137.0	0.47	<0.05	5.54	0.282	0.28	2.0	85
8350		47.6	<0.002	0.22	0.20	10.6	1	0.8	129.5	0.47	<0.05	6.11	0.255	0.37	2.0	75
8351		137.0	0.004	0.13	0.34	14.0	1	1.4	142.5	0.69	0.06	9.05	0.386	1.02	3.6	116
8352		140.5	0.002	0.12	0.36	16.1	1	2.0	111.5	0.85	0.06	13.45	0.406	1.07	5.3	126
8353		92.1	<0.002	0.06	0.27	11.8	1	1.1	88.9	0.64	<0.05	8.18	0.307	0.69	3.0	86
8354		30.9	<0.002	0.20	0.25	7.2	<1	0.7	73.1	0.50	0.05	4.90	0.186	0.22	2.3	46
8355		36.7	<0.002	0.08	0.24	8.2	<1	1.0	57.2	0.64	<0.05	5.94	0.237	0.26	2.2	62
8356		40.3	<0.002	0.28	0.25	6.4	<1	0.9	65.4	0.51	<0.05	4.39	0.181	0.25	1.6	50
8357		24.3	<0.002	0.85	0.23	3.7	<1	0.5	74.5	0.24	0.08	2.33	0.090	0.15	1.0	26
8358		35.0	<0.002	0.41	0.21	4.4	<1	0.7	81.3	0.45	0.05	3.73	0.137	0.24	1.4	33
8359		97.8	<0.002	0.16	0.24	11.8	<1	1.2	98.8	0.60	<0.05	7.21	0.306	0.55	3.0	93
8360		115.5	<0.002	0.17	0.22	13.4	1	1.3	105.5	0.67	<0.05	8.57	0.328	0.59	3.4	97
8361		10.4	0.041	8.73	3.27	7.8	22	2.5	182.0	0.29	4.13	1.04	0.536	0.18	0.3	78
8362		62.5	<0.002	0.10	0.27	8.9	1	1.0	60.5	0.61	<0.05	6.72	0.250	0.36	2.9	68
8363		23.1	<0.002	0.36	0.21	4.8	<1	0.7	60.4	0.30	<0.05	3.08	0.112	0.16	1.5	33
8364		20.6	<0.002	0.17	0.18	3.4	<1	0.7	62.5	0.34	<0.05	3.18	0.109	0.14	0.9	28
8365		24.3	<0.002	0.46	0.20	5.6	1	0.8	59.8	0.34	0.07	3.53	0.151	0.15	1.2	41
8366		44.2	<0.002	0.06	0.31	14.0	<1	1.2	107.5	0.73	0.05	9.32	0.363	0.27	3.6	105
8367		31.7	<0.002	0.08	0.23	12.5	<1	1.1	99.9	0.60	<0.05	8.68	0.326	0.18	4.1	96
8368		20.8	<0.002	0.15	0.25	12.8	<1	1.1	92.8	0.56	0.05	8.07	0.311	0.11	3.3	95
8369		46.8	<0.002	0.09	0.20	11.9	<1	1.2	104.5	0.53	<0.05	8.42	0.299	0.23	3.4	95
8370		37.1	<0.002	0.10	0.22	11.4	1	1.1	98.4	0.51	<0.05	7.56	0.288	0.19	3.3	86
8371		22.9	<0.002	0.19	0.21	11.4	<1	1.2	89.1	0.59	0.07	7.89	0.292	0.14	3.3	83
8372		11.6	<0.002	0.48	0.19	10.5	1	1.2	76.8	0.59	0.14	7.24	0.283	0.08	3.1	80
8373		13.1	<0.002	0.26	0.20	11.0	1	1.2	78.9	0.60	<0.05	7.85	0.308	0.11	3.4	80
8374		20.5	<0.002	0.39	0.18	11.1	1	1.0	95.3	0.57	0.08	6.88	0.315	0.13	3.4	86
8375		0.2	<0.002	<0.01	0.16	0.2	1	<0.2	83.4	<0.05	<0.05	0.09	0.006	<0.02	0.2	1
8376		46.7	<0.002	0.15	0.20	12.2	1	1.3	125.0	0.57	<0.05	6.84	0.330	0.31	3.1	95
8377		18.4	<0.002	0.18	0.21	8.9	1	1.1	80.4	0.69	0.05	8.23	0.280	0.13	3.8	72
8378		35.2	<0.002	0.09	0.19	10.3	<1	1.3	93.3	0.75	0.05	9.15	0.326	0.20	4.1	87
8379		35.9	<0.002	0.21	0.15	6.9	<1	1.7	81.7	0.57	0.08	6.66	0.210	0.27	2.9	58
8380		19.2	<0.002	1.98	0.18	6.1	2	2.1	46.0	0.31	0.21	3.89	0.109	0.15	1.5	110
8381		22.2	<0.002	0.75	0.20	8.2	1	3.5	63.2	0.39	0.09	6.26	0.184	0.18	3.2	108
8382		28.0	<0.002	0.60	0.24	8.6	1	2.9	56.0	0.60	0.05	8.08	0.250	0.23	4.3	80
8383		19.9	<0.002	0.24	0.20	10.9	<1	1.6	91.1	0.69	0.07	8.54	0.316	0.16	3.8	94
8384		27.4	<0.002	0.13	0.19	11.6	<1	1.4	98.8	0.75	0.07	9.17	0.334	0.15	4.1	87

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: BATTERY MINERAL RESOURCES LTD.
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 5-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18114878

Sample Description	Method / Analyte / Units / LOR	ME-MS61 W ppm 0.1	ME-MS61 Y ppm 0.1	ME-MS61 Zn ppm 2	ME-MS61 Zr ppm 0.5	Ag-OG62 Ag ppm 1	Cu-OG62 Cu % 0.001	Ni-OG62 Ni % 0.001	CRU-QC Pass2mm % 0.01	PUL-QC Pass75um % 0.01
8345		1.0	12.9	17	89.4				66.1	94.0
8346		1.3	12.9	17	111.0					97.7
8347		0.5	11.3	10	92.9					
8348		0.4	11.2	10	101.0					
8349		0.5	12.9	20	93.7				74.3	
8350		0.3	12.2	55	98.0					
8351		1.2	13.9	81	146.0					
8352		1.7	15.2	68	120.0					
8353		0.7	11.3	59	131.0					
8354		0.2	8.9	20	101.5					
8355		0.2	9.6	17	127.5					
8356		0.2	7.9	11	93.0					
8357		0.1	4.7	7	47.5					
8358		0.1	5.4	8	71.2					
8359		1.0	11.3	15	124.5					
8360		1.2	13.1	16	143.0					
8361		2.3	8.9	139	48.5		1.675	4.59		
8362		0.7	10.1	15	128.5					93.6
8363		0.2	6.1	10	52.8					95.2
8364		0.1	3.9	9	58.9					
8365		0.3	6.1	12	70.7					
8366		0.8	13.7	54	162.0					
8367		0.9	12.6	17	146.5					
8368		0.6	13.4	15	160.0					
8369		1.1	11.9	15	140.5					
8370		0.9	13.5	13	136.0					
8371		0.7	11.7	13	137.5					
8372		0.5	12.5	12	141.0					
8373		0.3	13.4	12	161.0					
8374		0.6	12.1	14	152.5					
8375		0.1	2.1	2	2.1					
8376		0.8	12.7	17	146.5					
8377		0.5	13.2	11	157.0					
8378		1.3	12.5	12	175.5					
8379		0.5	8.3	9	121.0					
8380		1.0	4.2	6	56.2					
8381		1.2	29.1	6	116.5					
8382		1.1	68.8	7	163.0					
8383		0.8	14.2	12	169.0					
8384		0.9	13.8	12	170.0				71.8	94.5

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: BATTERY MINERAL RESOURCES LTD.
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 5-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18114878

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	ME-MS61 Ag ppm 0.01	ME-MS61 Al % 0.01	ME-MS61 As ppm 0.2	ME-MS61 Ba ppm 10	ME-MS61 Be ppm 0.05	ME-MS61 Bi ppm 0.01	ME-MS61 Ca % 0.01	ME-MS61 Cd ppm 0.02	ME-MS61 Ce ppm 0.01	ME-MS61 Co ppm 0.1	ME-MS61 Cr ppm 1	ME-MS61 Cs ppm 0.05	ME-MS61 Cu ppm 0.2	ME-MS61 Fe % 0.01
8385		1.66	0.01	7.39	1.8	160	1.51	0.12	0.35	<0.02	50.5	23.1	104	0.42	4.4	3.77
8386		2.31	0.08	7.28	5.9	300	1.87	0.32	0.47	<0.02	51.6	50.7	105	0.87	47.0	3.75
8387		2.47	0.02	7.03	2.8	260	1.72	0.26	0.56	<0.02	48.6	13.3	94	0.65	3.9	3.17
8388		1.24	0.01	6.79	1.9	270	1.90	0.18	0.58	<0.02	59.5	13.7	78	0.73	18.4	2.90
8389		1.95	0.01	7.07	1.6	330	1.71	0.34	0.56	<0.02	71.1	17.0	90	0.66	4.3	3.71
8390		1.07	<0.01	7.73	1.1	700	2.66	0.19	0.41	<0.02	59.8	19.5	116	1.27	2.2	3.76
8391		1.25	0.03	6.50	2.3	310	1.96	0.79	0.22	<0.02	32.8	53.8	92	1.18	17.4	3.98
8392		2.38	0.02	3.32	10.8	70	0.77	0.91	0.23	<0.02	4.85	101.5	48	0.21	12.2	1.86
8393		2.16	0.02	4.18	19.4	20	0.85	0.69	0.13	<0.02	8.23	201	43	0.09	8.0	3.49
8394		2.54	0.05	5.67	10.6	40	0.91	1.70	0.23	<0.02	5.09	136.0	70	0.17	13.1	2.90
8395		0.59	0.03	6.69	0.6	520	1.83	0.21	0.18	<0.02	28.6	35.1	80	0.71	11.1	3.41
8396		1.12	0.08	5.35	2.1	140	1.05	0.72	0.19	<0.02	8.35	52.2	78	0.36	13.9	2.21
8397		1.23	0.04	3.63	7.1	30	0.65	1.68	0.46	<0.02	2.99	123.0	49	0.22	13.2	2.04
8398		1.36	0.01	5.56	2.2	40	1.44	0.33	0.18	<0.02	3.31	32.6	67	0.47	5.0	2.68
8399		0.60	0.01	0.27	3.1	10	12.90	0.30	0.44	<0.02	8.00	60.2	24	0.08	2.1	4.90
8400		0.60	0.02	0.27	3.5	10	11.25	0.38	0.38	<0.02	7.20	58.5	27	0.07	2.5	3.32
8401		0.07	>100	5.30	1690	260	0.53	17.00	0.27	13.35	22.3	93.8	34	1.56	>10000	3.58
8402		2.45	0.02	0.21	4.0	10	6.74	0.25	0.28	<0.02	5.63	35.9	34	0.06	3.1	3.83
8403		1.61	0.10	0.29	2.0	10	4.88	0.31	0.25	<0.02	3.49	24.6	37	<0.05	7.4	1.84
8404		1.55	0.07	0.72	1.4	10	3.12	0.23	0.24	<0.02	2.32	19.5	51	0.05	6.3	1.55
8405		1.72	0.07	3.66	4.1	30	1.29	0.62	0.24	<0.02	4.58	74.7	64	0.43	5.2	2.61
8406		1.43	0.03	3.25	3.0	20	0.89	0.36	0.33	<0.02	3.50	76.7	74	0.32	6.2	5.37
8407		2.15	0.02	6.40	4.1	30	1.01	0.17	0.24	<0.02	5.66	71.9	103	0.58	6.9	3.09
8408		2.43	0.04	5.85	3.7	30	0.97	0.47	0.35	<0.02	4.57	92.5	101	0.43	4.0	4.85
8409		2.08	0.03	6.47	2.2	30	1.19	0.25	0.36	<0.02	11.25	40.4	107	0.18	4.0	3.47
8410		2.14	0.03	5.85	5.2	90	1.51	0.67	0.52	<0.02	18.55	49.2	92	0.89	10.4	4.64
8411		1.26	0.23	6.85	8.4	150	1.54	0.96	0.30	<0.02	24.9	67.7	114	1.64	21.5	4.24
8412		1.18	0.04	3.48	8.0	30	1.06	1.78	0.21	<0.02	3.97	134.0	63	0.26	20.1	4.25
8413		1.65	0.05	3.41	6.0	80	1.12	1.56	0.20	<0.02	4.91	86.0	67	0.47	14.6	3.89
8414		2.33	0.03	2.15	3.7	50	1.28	1.03	1.13	<0.02	5.05	63.2	45	0.57	9.8	16.85
8415		2.02	0.03	5.85	8.6	120	1.51	0.96	2.23	<0.02	34.0	31.4	68	1.01	37.6	4.27
8416		2.07	0.05	5.99	15.5	110	1.50	1.85	2.90	<0.02	45.6	35.6	62	0.60	43.6	4.82
8417		2.12	0.19	5.61	13.4	230	1.24	5.95	4.58	0.06	43.7	35.6	54	0.68	99.3	5.24
8418		2.18	0.09	5.79	14.7	190	1.01	5.35	3.47	0.03	43.5	55.0	66	0.52	299	4.59
8419		2.03	0.06	5.73	6.7	370	1.26	7.72	4.25	0.05	53.5	33.7	56	0.61	40.1	3.67
8420		2.16	0.10	5.40	12.0	310	1.32	31.1	8.51	0.03	51.4	43.9	58	0.47	124.0	7.43
8421		2.21	0.24	5.87	6.5	410	1.11	14.20	5.11	0.05	41.0	26.8	54	0.64	54.0	4.09
8422		2.16	0.13	5.41	15.4	530	1.53	2.46	5.69	0.04	41.2	32.3	48	0.66	32.9	5.36
8423		2.08	0.02	6.36	9.8	420	1.85	0.79	4.59	<0.02	47.6	25.3	61	0.53	45.3	5.66
8424		2.10	0.03	5.92	19.9	340	1.72	0.89	4.57	<0.02	37.2	22.3	54	0.64	12.8	4.07

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: BATTERY MINERAL RESOURCES LTD.
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 5-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18114878

Sample Description	Method / Analyte / Units / LOR	ME-MS61 Ga ppm 0.05	ME-MS61 Ge ppm 0.05	ME-MS61 Hf ppm 0.1	ME-MS61 In ppm 0.005	ME-MS61 K % 0.01	ME-MS61 La ppm 0.5	ME-MS61 Li ppm 0.2	ME-MS61 Mg % 0.01	ME-MS61 Mn ppm 5	ME-MS61 Mo ppm 0.05	ME-MS61 Na % 0.01	ME-MS61 Nb ppm 0.1	ME-MS61 Ni ppm 0.2	ME-MS61 P ppm 10	ME-MS61 Pb ppm 0.5
8385		17.70	0.07	4.9	0.024	0.55	23.8	10.7	1.89	165	1.53	3.97	6.4	37.3	470	2.5
8386		17.60	0.16	4.8	0.027	1.00	25.2	13.7	1.96	203	1.50	3.41	7.3	39.8	490	3.0
8387		17.50	0.16	4.4	0.023	0.84	24.3	13.2	1.87	207	1.24	3.49	7.0	40.7	460	3.2
8388		16.40	0.16	3.8	0.023	0.98	29.8	11.8	1.63	199	1.41	3.33	6.5	34.6	400	4.8
8389		18.20	0.17	3.7	0.027	1.16	36.2	14.6	2.04	258	2.90	3.15	6.5	45.9	490	2.5
8390		22.0	0.16	4.3	0.051	2.24	25.9	16.6	1.99	223	0.63	2.58	8.9	43.5	530	2.3
8391		17.20	0.11	3.8	0.032	1.60	14.5	13.9	1.86	234	3.16	2.63	6.9	37.8	390	3.6
8392		8.13	0.07	1.4	0.008	0.30	2.3	3.9	0.48	83	4.24	2.07	2.3	24.2	170	4.3
8393		9.27	0.07	1.5	<0.005	0.20	3.8	2.7	0.39	68	1.52	2.94	2.5	21.2	180	4.0
8394		14.70	0.10	2.9	0.008	0.34	2.4	6.0	0.83	138	2.55	3.70	4.7	25.4	320	3.3
8395		17.25	0.13	3.8	0.033	2.84	13.3	14.0	1.71	226	1.02	1.88	6.4	38.4	410	3.0
8396		13.20	0.12	3.5	0.012	0.97	3.9	7.5	0.91	146	2.24	3.25	5.1	21.5	340	3.0
8397		7.83	0.11	1.4	<0.005	0.20	1.4	2.7	0.35	97	2.64	2.53	2.2	10.6	170	2.5
8398		13.30	0.11	3.0	0.007	0.31	1.4	4.5	0.63	106	1.91	3.86	4.4	15.6	310	1.8
8399		3.11	0.11	0.1	0.006	0.08	1.5	1.4	0.17	85	5.43	0.08	0.1	9.7	20	3.0
8400		2.74	0.08	<0.1	<0.005	0.07	1.3	1.3	0.16	81	5.54	0.09	0.1	9.0	20	3.1
8401		31.2	0.25	2.8	3.98	1.01	8.5	20.0	0.04	94	4.76	0.55	6.8	1540	500	1420
8402		2.04	0.07	<0.1	<0.005	0.08	1.4	1.3	0.13	62	12.15	0.04	0.2	6.4	10	2.3
8403		1.63	<0.05	0.1	<0.005	0.09	0.9	0.9	0.11	61	9.46	0.11	0.2	4.3	20	1.7
8404		2.31	<0.05	0.3	<0.005	0.08	0.6	0.8	0.11	52	8.46	0.47	0.4	4.0	50	1.8
8405		9.54	0.06	1.9	0.006	0.22	2.0	3.3	0.53	93	13.20	2.47	3.0	17.5	200	3.4
8406		9.28	0.05	2.1	0.010	0.18	1.6	3.7	0.62	104	4.35	2.03	2.8	24.3	210	4.3
8407		16.45	0.08	4.0	0.013	0.26	2.6	7.2	1.24	143	2.81	4.12	6.1	37.0	380	2.2
8408		14.35	0.10	3.8	0.011	0.22	2.1	6.1	1.08	134	4.26	3.71	5.3	29.5	370	3.1
8409		17.20	0.10	4.4	0.014	0.22	5.4	9.2	1.60	167	5.86	3.83	6.9	40.7	450	2.3
8410		18.55	0.10	3.1	0.018	0.53	8.2	7.9	1.18	157	5.26	3.45	5.6	35.6	340	2.7
8411		24.3	0.11	3.9	0.023	0.93	11.0	10.9	1.60	192	9.33	3.81	7.5	53.1	440	2.5
8412		9.92	0.07	2.1	0.009	0.25	1.8	2.3	0.32	68	4.92	2.50	2.8	18.8	220	2.4
8413		10.15	0.07	2.0	0.013	0.38	2.3	3.7	0.48	97	7.96	2.16	3.0	20.6	200	2.5
8414		8.83	0.07	1.1	0.015	0.32	2.3	3.0	0.40	151	12.65	1.29	2.1	15.0	120	1.9
8415		14.20	0.10	2.8	0.055	0.66	16.6	9.3	1.25	300	2.68	3.40	4.2	25.1	350	2.8
8416		14.25	0.12	2.9	0.081	0.56	23.4	9.9	1.41	388	1.79	3.21	4.3	29.8	410	3.4
8417		12.45	0.10	2.2	0.121	0.79	22.9	11.1	1.46	542	0.87	2.57	4.2	32.0	460	7.7
8418		13.80	0.11	2.7	0.123	0.79	22.2	11.5	1.40	471	1.13	2.82	4.2	27.6	410	6.7
8419		13.20	0.11	2.9	0.088	1.35	26.6	9.5	0.91	459	1.13	2.65	4.4	19.6	450	8.2
8420		17.30	0.09	2.8	0.117	1.17	26.0	16.1	1.74	945	0.62	1.60	4.9	29.2	840	5.2
8421		13.80	0.12	2.9	0.070	1.73	20.4	10.2	0.96	547	0.85	2.49	4.5	13.9	580	12.4
8422		13.65	0.09	2.3	0.113	1.76	20.7	13.1	1.35	649	0.94	1.47	4.2	18.4	520	8.8
8423		15.90	0.11	2.8	0.103	1.51	23.6	10.5	1.09	521	1.06	2.84	5.3	18.4	580	4.3
8424		14.50	0.11	2.9	0.077	1.38	18.7	12.2	1.30	518	0.88	2.47	4.5	16.0	540	4.6

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: BATTERY MINERAL RESOURCES LTD.
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 5-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18114878

Sample Description	Method / Analyte / Units / LOR	ME-MS61 Rb ppm 0.1	ME-MS61 Re ppm 0.002	ME-MS61 S % 0.01	ME-MS61 Sb ppm 0.05	ME-MS61 Sc ppm 0.1	ME-MS61 Se ppm 1	ME-MS61 Sn ppm 0.2	ME-MS61 Sr ppm 0.2	ME-MS61 Ta ppm 0.05	ME-MS61 Te ppm 0.05	ME-MS61 Th ppm 0.01	ME-MS61 Ti % 0.005	ME-MS61 Tl ppm 0.02	ME-MS61 U ppm 0.1	ME-MS61 V ppm 1
8385		21.5	<0.002	0.08	0.15	10.7	1	1.2	93.5	0.69	<0.05	8.44	0.312	0.12	3.6	84
8386		49.3	<0.002	0.19	0.19	12.3	<1	1.2	109.5	0.76	0.06	8.76	0.324	0.26	3.7	86
8387		41.4	0.002	0.09	0.15	12.1	<1	1.3	122.0	0.70	<0.05	9.38	0.307	0.23	3.9	85
8388		49.7	<0.002	0.13	0.15	10.3	<1	1.1	149.5	0.57	<0.05	13.35	0.261	0.26	3.7	74
8389		55.2	<0.002	0.13	0.14	12.0	<1	1.2	100.5	0.64	<0.05	10.10	0.305	0.30	3.2	90
8390		115.0	<0.002	0.01	0.15	17.1	<1	2.0	82.8	0.89	<0.05	12.15	0.393	0.51	4.0	120
8391		74.0	<0.002	0.11	0.17	10.4	1	1.5	73.8	0.63	0.11	9.83	0.271	0.45	4.5	91
8392		12.8	<0.002	0.56	0.30	2.9	1	0.5	35.8	0.23	0.07	3.11	0.086	0.10	3.8	28
8393		7.4	<0.002	1.15	0.15	3.7	1	0.6	35.3	0.29	0.15	3.32	0.081	0.07	3.7	37
8394		14.1	<0.002	0.63	0.16	6.1	1	0.8	48.8	0.51	0.11	5.59	0.187	0.11	3.6	50
8395		137.0	<0.002	0.01	0.20	11.4	<1	1.2	49.1	0.62	0.05	8.95	0.278	0.83	4.3	96
8396		46.9	<0.002	0.19	0.17	6.9	<1	0.8	47.2	0.53	0.08	6.64	0.213	0.33	3.2	49
8397		9.2	<0.002	0.71	0.18	2.7	1	0.4	35.2	0.25	0.07	2.74	0.092	0.08	2.7	23
8398		17.1	<0.002	0.14	0.15	4.7	<1	1.0	43.9	0.48	<0.05	5.62	0.176	0.12	3.1	46
8399		3.5	<0.002	0.35	0.33	3.2	1	1.6	11.2	<0.05	<0.05	2.28	<0.005	0.02	0.5	43
8400		3.3	<0.002	0.32	0.34	2.5	<1	1.3	11.6	<0.05	<0.05	2.96	<0.005	0.02	0.4	26
8401		30.6	0.002	8.38	308	5.1	78	2.9	355	0.51	35.6	3.94	0.178	14.75	2.5	39
8402		3.8	0.002	0.17	0.32	2.4	1	1.6	7.2	<0.05	0.05	1.62	<0.005	0.03	0.5	36
8403		3.6	<0.002	0.13	0.33	1.3	<1	1.0	6.9	<0.05	<0.05	1.20	0.005	0.03	0.7	21
8404		2.9	0.002	0.08	0.33	1.2	<1	0.6	11.5	<0.05	<0.05	1.21	0.018	0.02	1.1	17
8405		12.5	<0.002	0.34	0.23	4.6	1	1.0	28.9	0.31	0.09	4.46	0.133	0.11	4.3	41
8406		9.3	<0.002	0.40	0.30	6.1	1	1.0	28.0	0.30	0.05	4.04	0.143	0.06	2.2	72
8407		15.7	<0.002	0.27	0.16	8.9	<1	1.4	53.3	0.61	<0.05	7.62	0.271	0.11	3.8	67
8408		12.0	<0.002	0.40	0.18	8.6	<1	1.8	42.6	0.56	<0.05	6.47	0.258	0.07	3.4	72
8409		10.1	0.002	0.11	0.15	10.2	<1	2.0	56.7	0.72	<0.05	8.58	0.302	0.07	5.0	56
8410		30.0	<0.002	0.26	0.20	9.3	<1	1.4	63.6	0.56	<0.05	8.93	0.248	0.18	4.2	72
8411		52.6	<0.002	0.35	0.25	11.5	1	1.6	58.8	0.77	0.08	10.55	0.333	0.30	6.3	85
8412		12.1	0.003	0.75	0.20	4.0	1	0.9	23.1	0.28	0.05	3.95	0.124	0.08	4.0	39
8413		18.1	<0.002	0.54	0.19	3.9	1	1.1	23.0	0.31	<0.05	4.37	0.143	0.10	3.9	45
8414		17.6	0.004	0.42	0.19	13.1	1	1.6	25.7	0.18	<0.05	3.41	0.093	0.12	2.7	104
8415		37.5	<0.002	0.26	0.20	8.6	<1	1.2	91.1	0.38	<0.05	6.68	0.189	0.23	2.7	59
8416		28.7	<0.002	0.26	0.21	9.2	<1	0.9	102.0	0.39	<0.05	7.02	0.208	0.17	2.6	64
8417		35.8	<0.002	0.24	0.19	9.1	<1	0.8	104.5	0.38	0.14	5.73	0.215	0.18	1.9	63
8418		32.7	<0.002	0.15	0.16	9.4	<1	0.7	83.6	0.39	0.19	5.50	0.227	0.18	2.2	66
8419		42.7	0.002	0.10	0.14	7.3	<1	0.9	88.3	0.39	0.22	7.05	0.189	0.22	2.9	53
8420		32.5	<0.002	0.25	0.19	6.4	<1	3.6	83.9	0.44	0.36	7.74	0.173	0.14	3.2	50
8421		46.2	<0.002	0.05	0.15	5.7	<1	1.0	67.3	0.43	0.35	6.26	0.160	0.22	2.9	37
8422		54.6	<0.002	0.27	0.22	5.0	1	1.1	80.3	0.38	0.33	6.67	0.137	0.24	2.7	35
8423		45.6	<0.002	0.12	0.19	5.9	<1	1.7	77.1	0.49	0.09	8.79	0.174	0.21	3.4	43
8424		47.7	<0.002	0.22	0.18	5.6	<1	0.8	68.8	0.40	0.17	7.17	0.150	0.23	2.9	37

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: BATTERY MINERAL RESOURCES LTD.
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 5-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18114878

Sample Description	Method / Analyte / Units / LOR	ME-MS61 W ppm 0.1	ME-MS61 Y ppm 0.1	ME-MS61 Zn ppm 2	ME-MS61 Zr ppm 0.5	Ag-OG62 Ag ppm 1	Cu-OG62 Cu % 0.001	Ni-OG62 Ni % 0.001	CRU-QC Pass2mm % 0.01	PUL-QC Pass75um % 0.01
8385		0.9	14.0	13	170.5					
8386		0.9	15.9	18	175.0					
8387		0.7	14.9	17	153.0					
8388		0.6	14.5	17	130.0					
8389		0.9	14.9	22	132.0					
8390		1.8	13.3	21	149.5					
8391		0.6	9.8	17	134.5					
8392		0.2	2.6	5	51.4					
8393		0.8	4.4	4	52.8					
8394		0.8	3.7	11	103.5					
8395		1.9	8.2	20	139.0					
8396		1.3	5.0	13	124.5					
8397		0.2	2.7	6	52.0					
8398		0.3	7.7	9	103.5					
8399		0.3	82.2	4	2.8					
8400		0.2	73.7	4	2.5					
8401		27.9	4.4	2210	95.0	1025	5.19			
8402		0.3	41.8	3	2.1					
8403		0.2	31.1	3	2.6					
8404		0.4	18.5	2	11.0					
8405		1.0	8.4	7	73.9					
8406		1.8	5.1	10	73.3					
8407		1.2	5.4	15	140.0					
8408		1.0	6.4	14	134.0					
8409		0.7	7.1	19	149.0					
8410		0.5	8.6	17	108.5					
8411		0.7	9.2	23	134.5					
8412		1.0	6.3	6	73.5					
8413		1.1	5.9	8	66.9					
8414		1.3	7.8	10	40.3					
8415		0.3	9.2	25	102.0					
8416		0.4	11.3	35	104.5					
8417		0.4	13.1	64	80.1					
8418		0.3	10.6	62	93.5					
8419		0.4	11.3	51	104.0					
8420		0.4	19.7	66	104.0					
8421		0.3	10.6	47	101.5					
8422		0.5	10.9	53	84.9					
8423		0.5	11.7	35	98.4					
8424		0.5	11.7	34	104.5				73.8	89.3

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: BATTERY MINERAL RESOURCES LTD.
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 5-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18114878

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	ME-MS61 Ag ppm 0.01	ME-MS61 Al % 0.01	ME-MS61 As ppm 0.2	ME-MS61 Ba ppm 10	ME-MS61 Be ppm 0.05	ME-MS61 Bi ppm 0.01	ME-MS61 Ca % 0.01	ME-MS61 Cd ppm 0.02	ME-MS61 Ce ppm 0.01	ME-MS61 Co ppm 0.1	ME-MS61 Cr ppm 1	ME-MS61 Cs ppm 0.05	ME-MS61 Cu ppm 0.2	ME-MS61 Fe % 0.01
8425		1.04	<0.01	0.06	0.3	10	0.07	0.02	32.4	<0.02	0.91	0.8	2	<0.05	2.9	0.10
8426		2.13	0.06	5.62	17.6	130	1.27	0.43	6.29	<0.02	51.8	42.5	57	0.69	255	5.26
8427		1.98	0.02	6.24	16.2	120	1.14	0.37	1.70	<0.02	43.9	45.7	66	0.37	7.9	3.40
8428		1.45	0.03	6.80	14.2	350	1.88	0.66	0.64	<0.02	55.0	52.5	71	0.83	29.3	3.66
8429		1.31	0.08	6.90	7.5	70	1.40	0.28	1.53	<0.02	35.4	32.4	72	0.48	71.2	6.68
8430		2.09	0.08	6.71	12.5	80	1.10	0.97	0.86	<0.02	37.4	126.0	85	0.68	34.7	2.63
8431		2.15	0.13	7.47	23.0	50	1.52	0.71	2.22	<0.02	19.50	35.8	72	0.21	25.8	5.98
8432		1.50	0.04	5.78	7.6	30	2.85	0.84	1.17	<0.02	3.69	240	46	0.06	8.2	8.14
8433		2.04	0.02	0.21	2.4	10	2.16	0.26	0.27	<0.02	1.73	29.7	35	<0.05	3.0	2.28
8434		2.12	0.03	1.47	5.1	20	1.00	0.47	0.36	<0.02	2.06	94.9	35	0.06	7.2	4.00
8435		2.12	0.03	3.48	5.7	20	0.79	0.38	0.49	<0.02	3.42	87.9	46	0.05	7.3	6.50
8436		2.24	0.05	4.76	5.5	10	1.30	0.58	0.52	<0.02	7.21	74.7	46	0.06	6.0	14.00
8437		1.70	0.04	4.90	7.5	10	1.38	0.51	0.71	<0.02	6.81	122.5	45	0.07	4.7	9.65
8438		1.72	0.07	6.33	8.1	10	0.98	0.50	1.30	<0.02	5.79	186.0	59	0.06	5.5	8.13
8439		0.66	0.03	6.17	8.3	20	0.88	0.29	0.41	<0.02	4.10	130.0	46	0.08	7.7	10.50
8440		0.62	0.04	6.22	18.6	20	0.99	0.66	0.43	<0.02	4.53	255	45	0.08	8.3	12.00
8441		0.08	4.18	5.37	13.8	110	0.47	0.83	3.39	2.04	16.65	959	264	0.74	>10000	17.55
8442		1.82	0.07	1.13	12.2	10	2.37	0.71	0.08	<0.02	4.65	155.5	37	0.15	4.1	23.7
8443		1.69	0.03	1.17	3.2	10	1.22	0.23	0.31	<0.02	2.59	58.3	31	0.06	7.2	9.06
8444		1.97	0.09	3.67	11.6	20	0.47	0.72	0.09	<0.02	1.31	172.5	35	0.07	3.4	17.20
8445		1.68	0.08	8.03	19.1	20	0.79	1.01	0.54	<0.02	5.64	310	55	0.09	5.5	3.05
8446		1.29	0.15	7.57	19.7	20	0.94	2.86	0.75	<0.02	4.95	663	42	0.09	5.9	3.66
8447		2.03	0.07	7.96	14.3	10	0.82	1.52	1.39	<0.02	7.33	390	59	0.06	4.3	4.24
8448		2.16	0.05	7.78	23.3	30	0.85	1.69	1.29	<0.02	15.90	507	81	0.30	5.0	3.81
8449		2.84	0.19	6.86	34.4	140	1.37	1.81	0.55	<0.02	205	370	79	1.04	8.5	5.15
8450		1.23	0.04	5.65	11.3	320	1.93	1.29	0.43	<0.02	76.7	55.3	72	1.65	10.4	5.52
8451		2.10	0.04	6.55	15.2	650	2.42	0.60	0.25	<0.02	67.2	28.6	76	1.58	9.3	3.20
8452		2.12	0.02	6.40	12.8	620	2.35	0.48	0.58	<0.02	68.8	26.3	84	1.38	10.2	2.87
8453		2.01	0.02	6.07	10.3	400	2.08	0.65	1.42	0.02	81.7	25.8	69	1.17	9.7	2.87
8454		1.99	0.04	6.30	14.6	310	2.08	1.28	0.84	<0.02	66.7	43.8	71	1.05	8.0	3.61
8455		2.15	0.02	5.95	13.1	230	2.15	0.77	0.52	<0.02	23.6	49.6	73	1.17	7.2	6.86
8456		2.07	0.02	6.30	18.6	230	2.10	0.76	0.60	<0.02	32.4	51.0	79	1.27	4.7	4.29
8457		2.01	0.01	6.40	11.2	600	2.47	0.77	3.01	<0.02	91.8	22.4	75	1.94	7.7	3.78
8458		2.15	0.04	6.62	10.7	700	2.39	0.41	1.26	0.02	73.2	22.2	77	2.13	7.3	3.28
8459		1.99	0.04	6.73	9.1	660	2.23	0.46	1.63	<0.02	80.1	23.7	88	1.92	11.0	3.02
8460		2.07	0.03	6.66	23.4	660	2.32	0.59	1.14	0.02	70.9	29.0	82	2.63	5.6	3.90
8461		2.19	0.05	6.26	14.2	810	1.79	0.58	1.47	<0.02	78.9	26.0	72	2.57	21.9	3.04
8462		1.94	0.05	6.40	12.5	1130	2.08	0.47	1.63	<0.02	84.7	20.0	71	2.35	45.7	2.80
8463		1.98	0.09	6.73	26.7	1180	1.85	0.38	1.33	0.03	73.6	20.9	78	2.82	203	2.63
8464		1.71	0.13	7.23	45.0	1660	2.24	0.80	1.22	0.02	137.0	28.8	103	5.20	45.4	4.10

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: BATTERY MINERAL RESOURCES LTD.
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 5-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18114878

Sample Description	Method / Analyte / Units / LOR	ME-MS61 Ga ppm 0.05	ME-MS61 Ge ppm 0.05	ME-MS61 Hf ppm 0.1	ME-MS61 In ppm 0.005	ME-MS61 K % 0.01	ME-MS61 La ppm 0.5	ME-MS61 Li ppm 0.2	ME-MS61 Mg % 0.01	ME-MS61 Mn ppm 5	ME-MS61 Mo ppm 0.05	ME-MS61 Na % 0.01	ME-MS61 Nb ppm 0.1	ME-MS61 Ni ppm 0.2	ME-MS61 P ppm 10	ME-MS61 Pb ppm 0.5
8425		0.27	0.12	0.1	<0.005	0.01	1.1	1.2	1.25	82	0.20	0.03	0.1	5.0	50	<0.5
8426		13.55	0.10	2.7	0.078	0.84	25.0	17.2	1.95	739	0.57	2.37	4.4	18.1	780	3.7
8427		14.75	0.11	2.9	0.029	0.69	21.3	9.6	1.14	289	2.27	3.87	4.8	15.4	500	2.5
8428		18.00	0.14	3.4	0.052	1.54	28.1	8.3	0.92	166	5.00	3.68	5.4	20.0	430	3.1
8429		17.70	0.10	3.5	0.021	0.51	17.1	4.8	0.53	168	26.7	4.97	5.8	13.0	400	3.2
8430		16.90	0.14	4.1	0.016	0.62	18.4	6.0	0.68	149	15.55	4.82	5.3	19.2	500	3.0
8431		18.65	0.11	3.8	0.022	0.46	8.7	3.1	0.35	187	37.3	5.91	4.1	9.9	460	4.2
8432		12.15	0.09	1.9	0.005	0.27	1.5	0.9	0.08	103	9.93	4.55	1.6	12.5	310	3.8
8433		1.17	0.05	0.1	<0.005	0.07	0.5	0.8	0.08	62	3.36	0.09	0.3	4.2	20	2.2
8434		4.15	0.08	0.7	0.009	0.15	0.9	1.2	0.12	73	6.87	1.06	1.0	8.7	90	3.3
8435		8.57	0.05	1.4	0.009	0.17	1.6	1.3	0.15	85	10.40	2.70	1.6	9.7	200	4.3
8436		12.05	0.05	2.0	0.012	0.15	3.4	1.9	0.19	107	13.25	3.77	2.0	11.3	310	3.7
8437		11.20	0.07	1.8	0.006	0.14	3.2	1.1	0.10	96	14.40	3.92	2.0	8.4	370	4.5
8438		13.80	0.07	2.6	0.008	0.16	2.5	1.0	0.07	128	21.9	5.16	2.7	11.2	510	3.7
8439		14.35	0.08	2.2	0.013	0.26	1.9	1.9	0.22	91	4.26	4.78	2.2	12.6	370	4.0
8440		14.40	0.07	2.3	0.011	0.27	2.1	1.9	0.17	82	4.83	4.85	2.3	25.5	370	4.1
8441		11.25	0.19	1.3	0.116	0.31	7.0	8.3	3.93	987	4.29	1.16	4.9	>10000	460	13.9
8442		4.89	0.07	0.3	0.009	0.15	1.8	1.7	0.13	94	24.5	0.77	2.8	17.6	60	3.3
8443		4.30	0.05	0.3	0.011	0.12	1.2	1.6	0.20	110	4.92	0.78	1.6	13.3	60	3.7
8444		7.93	0.07	0.9	<0.005	0.18	0.6	0.9	0.05	66	36.0	2.92	2.6	12.5	220	5.1
8445		16.00	0.06	2.6	0.007	0.25	2.7	1.6	0.18	76	45.8	6.65	2.8	16.0	470	4.1
8446		15.40	0.07	2.5	0.005	0.43	2.2	1.1	0.11	87	103.0	6.09	2.1	17.0	430	8.1
8447		16.65	0.08	3.8	0.007	0.25	3.2	0.8	0.07	132	40.8	6.76	2.9	8.9	520	4.5
8448		20.7	0.10	5.7	0.006	0.43	7.5	2.8	0.28	145	16.05	6.22	5.3	25.1	610	3.5
8449		20.6	0.18	4.9	0.019	1.12	101.0	10.0	1.02	198	133.5	4.24	6.9	35.1	580	6.6
8450		16.25	0.12	3.5	0.023	1.85	39.3	10.9	1.06	210	4.92	2.59	6.6	28.6	360	3.9
8451		16.90	0.13	5.1	0.030	2.80	36.8	11.7	1.11	188	2.33	2.54	8.5	38.1	460	9.4
8452		16.25	0.15	6.5	0.018	2.74	36.2	10.6	0.99	196	2.83	2.79	8.5	28.0	500	5.2
8453		15.85	0.15	3.8	0.026	1.80	41.9	10.2	0.84	244	2.48	3.31	6.3	22.6	410	3.7
8454		17.45	0.14	3.9	0.024	1.54	33.3	9.2	0.81	203	3.28	3.69	6.6	29.4	440	4.7
8455		16.10	0.11	3.9	0.013	1.35	10.3	8.7	0.82	224	3.00	3.48	5.5	24.0	410	3.5
8456		15.50	0.11	4.3	0.014	1.35	14.6	8.9	0.81	222	3.32	3.78	6.5	24.6	440	3.5
8457		17.05	0.16	5.2	0.056	2.20	51.5	14.6	1.08	426	1.55	2.83	8.5	30.6	500	5.9
8458		18.70	0.15	5.3	0.043	2.50	40.0	14.6	1.25	297	1.71	2.59	9.4	35.5	460	9.5
8459		17.70	0.16	5.2	0.037	2.51	42.5	12.1	1.09	309	2.35	3.17	8.7	35.7	490	7.9
8460		18.95	0.14	6.2	0.032	2.66	38.9	15.6	1.33	352	1.93	2.52	9.8	34.0	510	6.6
8461		16.20	0.16	5.0	0.025	3.03	42.9	13.5	1.08	364	1.82	2.31	9.4	30.8	440	5.6
8462		17.15	0.17	5.4	0.038	4.05	45.2	13.6	1.11	399	1.96	1.94	10.7	30.0	440	6.3
8463		17.40	0.20	4.8	0.036	4.72	38.2	12.5	1.13	414	3.24	2.19	10.5	35.2	440	12.3
8464		20.4	0.22	4.7	0.053	4.94	82.0	19.0	1.76	605	3.40	2.33	10.6	56.2	500	15.6

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: BATTERY MINERAL RESOURCES LTD.
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 5-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18114878

Sample Description	Method / Analyte / Units / LOR	ME-MS61 Rb ppm 0.1	ME-MS61 Re ppm 0.002	ME-MS61 S % 0.01	ME-MS61 Sb ppm 0.05	ME-MS61 Sc ppm 0.1	ME-MS61 Se ppm 1	ME-MS61 Sn ppm 0.2	ME-MS61 Sr ppm 0.2	ME-MS61 Ta ppm 0.05	ME-MS61 Te ppm 0.05	ME-MS61 Th ppm 0.01	ME-MS61 Ti % 0.005	ME-MS61 Tl ppm 0.02	ME-MS61 U ppm 0.1	ME-MS61 V ppm 1
8425		0.3	<0.002	<0.01	0.08	0.2	1	<0.2	78.0	<0.05	<0.05	0.08	<0.005	<0.02	0.2	1
8426		34.0	<0.002	0.31	0.22	6.2	1	0.7	64.4	0.41	0.05	6.64	0.161	0.18	3.1	42
8427		23.4	<0.002	0.29	0.16	5.4	<1	0.8	43.4	0.46	0.06	7.15	0.168	0.13	3.2	37
8428		63.1	0.002	0.39	0.24	6.0	1	1.4	52.4	0.53	0.07	7.99	0.177	0.32	6.3	49
8429		23.8	0.006	0.22	0.30	5.3	1	1.7	47.0	0.50	0.06	9.37	0.178	0.14	12.5	119
8430		30.3	0.002	0.72	0.19	4.8	1	1.1	40.9	0.53	0.09	8.51	0.189	0.19	9.4	39
8431		16.2	0.008	0.28	0.28	4.7	1	2.1	55.8	0.42	0.11	9.11	0.152	0.12	18.5	76
8432		10.5	0.003	1.25	0.19	3.0	1	3.3	35.9	0.17	0.08	2.60	0.065	0.07	2.0	55
8433		2.7	0.002	0.21	0.40	0.9	1	0.8	5.8	<0.05	<0.05	0.63	0.005	0.02	0.4	16
8434		5.9	0.004	0.57	0.48	1.9	1	1.6	11.4	0.06	0.05	2.30	0.023	0.04	1.3	21
8435		7.0	0.002	0.45	0.39	3.3	1	3.3	16.6	0.13	0.05	4.22	0.053	0.05	2.8	64
8436		5.1	0.004	0.32	0.21	7.4	1	5.3	15.5	0.17	0.05	6.31	0.076	0.04	2.6	86
8437		4.3	0.002	0.59	0.21	3.6	1	2.2	17.9	0.16	0.08	10.40	0.056	0.02	1.7	65
8438		4.8	0.003	0.86	0.18	2.8	1	2.3	23.3	0.27	0.09	18.00	0.086	0.03	2.3	61
8439		9.8	0.002	0.56	0.21	4.2	1	5.4	16.6	0.22	0.06	8.50	0.077	0.07	3.5	73
8440		10.1	0.002	1.86	0.17	4.6	3	6.0	17.6	0.21	0.09	8.35	0.084	0.09	2.9	86
8441		10.1	0.049	8.55	2.89	8.1	21	2.6	183.0	0.32	4.45	1.09	0.514	0.16	0.3	78
8442		5.5	0.012	1.31	0.40	7.5	1	16.1	5.0	0.12	0.12	1.32	0.111	0.04	1.3	262
8443		3.8	<0.002	0.40	0.40	4.2	1	6.5	5.0	0.07	0.05	1.51	0.047	0.02	0.9	111
8444		6.5	0.016	0.83	0.20	5.3	1	12.5	9.6	0.16	0.17	1.79	0.083	0.05	2.9	214
8445		9.4	0.013	1.19	0.16	1.9	2	1.8	15.2	0.25	0.18	6.96	0.082	0.07	4.5	20
8446		19.9	0.018	2.57	0.21	1.3	3	0.6	18.2	0.25	0.38	7.68	0.062	0.14	8.1	15
8447		8.4	0.008	1.39	0.14	1.6	1	0.8	33.6	0.34	0.26	7.67	0.096	0.07	3.2	28
8448		17.0	0.002	1.94	0.14	2.6	2	0.8	27.2	0.60	0.15	7.06	0.179	0.11	3.8	29
8449		51.1	0.006	1.41	0.24	6.7	2	1.2	31.6	0.64	0.29	14.65	0.201	0.34	20.5	51
8450		89.0	<0.002	0.49	0.19	7.5	1	1.3	38.7	0.60	0.05	10.70	0.184	0.47	5.0	60
8451		106.5	<0.002	0.22	0.18	7.4	1	1.1	39.0	0.80	<0.05	12.60	0.226	0.51	5.8	47
8452		96.0	<0.002	0.18	0.18	7.7	1	1.3	46.9	0.82	0.05	15.85	0.230	0.50	6.4	47
8453		75.4	<0.002	0.27	0.17	6.9	1	1.1	52.0	0.57	0.07	11.35	0.185	0.41	4.5	47
8454		64.4	<0.002	0.40	0.28	7.5	1	1.3	48.8	0.59	0.08	12.65	0.189	0.34	5.8	49
8455		53.0	<0.002	0.48	0.19	7.1	1	1.4	35.1	0.55	<0.05	9.01	0.180	0.34	5.1	64
8456		58.9	<0.002	0.48	0.21	6.6	<1	1.3	41.5	0.62	0.05	10.95	0.198	0.34	5.1	42
8457		96.1	<0.002	0.26	0.20	8.0	1	1.8	76.3	0.75	0.05	15.20	0.227	0.59	5.6	55
8458		116.5	0.002	0.22	0.26	8.8	<1	1.1	44.4	0.85	0.05	15.05	0.226	0.67	5.8	54
8459		103.0	0.002	0.29	0.24	9.2	<1	1.5	50.1	0.80	<0.05	13.70	0.251	0.61	4.9	61
8460		126.0	<0.002	0.32	0.24	8.4	<1	1.5	43.8	0.85	<0.05	16.40	0.246	0.79	5.9	53
8461		125.0	<0.002	0.29	0.19	7.8	<1	1.5	48.2	0.80	0.05	16.35	0.216	0.84	5.3	47
8462		144.5	0.002	0.32	0.19	9.0	1	1.8	48.4	0.90	<0.05	15.30	0.229	0.93	5.5	55
8463		167.5	0.002	0.33	0.25	9.5	1	1.9	46.4	0.86	0.05	14.35	0.238	1.21	4.7	59
8464		220	0.003	0.57	0.30	15.8	1	2.1	83.6	0.89	0.07	15.70	0.298	1.91	4.6	87

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: BATTERY MINERAL RESOURCES LTD.
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 5-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18114878

Sample Description	Method / Analyte / Units / LOR	ME-MS61 W ppm 0.1	ME-MS61 Y ppm 0.1	ME-MS61 Zn ppm 2	ME-MS61 Zr ppm 0.5	Ag-OG62 Ag ppm 1	Cu-OG62 Cu % 0.001	Ni-OG62 Ni % 0.001	CRU-QC Pass2mm % 0.01	PUL-QC Pass75um % 0.01
8425		<0.1	1.7	3	1.6					
8426		0.3	15.4	43	97.7					
8427		0.4	9.3	24	104.5					
8428		4.1	9.2	17	121.5					
8429		0.8	8.5	10	126.0					89.3
8430		0.5	7.7	12	148.5					
8431		1.6	10.3	7	133.0					
8432		1.5	17.6	3	71.8					
8433		0.4	13.1	3	6.1					
8434		2.9	6.1	5	44.4					
8435		4.6	5.2	5	60.4					
8436		6.0	9.1	7	88.2					
8437		6.0	8.5	6	100.0					
8438		7.9	8.9	5	130.5					
8439		8.3	6.4	6	99.0					
8440		9.9	7.0	6	104.0					
8441		2.5	8.9	142	50.1		1.640	4.65		
8442		12.6	16.0	6	10.2					
8443		5.8	6.9	5	9.7					
8444		11.6	2.5	5	33.9					
8445		9.8	6.2	3	103.5					
8446		3.7	5.9	2	101.0					
8447		4.3	6.1	2	154.0					
8448		2.6	7.6	6	208					
8449		2.0	12.7	19	165.5					
8450		1.0	12.9	22	128.5					
8451		1.4	16.3	21	185.5					
8452		1.0	17.6	20	227					
8453		0.8	13.8	17	137.0					
8454		1.0	13.4	17	134.5					
8455		2.8	13.1	19	136.0					
8456		1.6	13.5	20	158.0					
8457		1.3	18.6	27	179.0					
8458		1.4	18.9	34	184.0					
8459		1.0	17.1	34	184.5					
8460		1.5	18.1	44	215					
8461		1.2	18.4	40	176.0					
8462		1.5	21.5	46	185.5					
8463		0.9	20.3	61	169.5					
8464		0.7	23.7	116	161.5				74.7	90.7

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: BATTERY MINERAL RESOURCES LTD.
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 5-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18114878

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	ME-MS61 Ag ppm 0.01	ME-MS61 Al % 0.01	ME-MS61 As ppm 0.2	ME-MS61 Ba ppm 10	ME-MS61 Be ppm 0.05	ME-MS61 Bi ppm 0.01	ME-MS61 Ca % 0.01	ME-MS61 Cd ppm 0.02	ME-MS61 Ce ppm 0.01	ME-MS61 Co ppm 0.1	ME-MS61 Cr ppm 1	ME-MS61 Cs ppm 0.05	ME-MS61 Cu ppm 0.2	ME-MS61 Fe % 0.01
8465		1.48	0.08	6.30	18.2	1210	2.79	1.05	3.84	0.03	88.6	26.4	76	4.42	33.1	6.45
8466		2.01	0.22	5.50	26.1	1490	2.29	1.72	4.32	0.05	53.3	49.6	58	1.18	455	5.45
8467		1.73	0.32	6.57	12.0	1470	3.38	1.19	3.26	0.10	87.2	25.1	89	1.19	55.3	4.19
8468		1.68	0.17	6.44	54.8	1310	2.60	2.04	1.92	0.03	100.0	21.8	74	2.33	30.9	2.62
8469		2.02	0.07	6.02	15.8	1240	2.13	0.64	3.30	0.02	66.5	19.5	63	2.32	20.0	4.27
8470		2.51	0.22	1.75	869	120	1.17	1.13	3.90	0.03	18.70	736	18	2.39	151.0	41.3
8471		2.56	0.50	1.27	2420	40	0.64	2.00	3.54	0.03	1.49	2010	12	0.87	333	44.7
8472		2.39	0.42	1.36	3500	90	0.93	2.23	3.02	<0.02	1.62	2860	14	1.71	290	43.4
8473		3.30	0.59	0.86	2210	50	0.86	4.95	3.08	0.04	1.11	1855	9	1.04	237	45.5
8474		1.82	0.04	3.67	711	370	2.84	0.56	3.60	<0.02	34.6	592	44	8.08	14.3	21.8
8475		1.00	<0.01	0.07	3.0	20	0.08	0.03	33.0	<0.02	1.03	4.0	2	0.06	1.6	0.23
8476		1.37	0.12	3.20	71.4	420	2.12	1.46	12.45	0.06	50.0	85.3	30	4.60	47.6	9.68
8477		1.79	0.13	3.37	74.4	280	1.92	2.67	12.45	0.08	63.0	108.5	30	4.13	168.5	10.15
8478		2.04	0.12	5.42	16.6	1090	2.07	0.23	3.62	0.06	97.9	10.6	40	1.47	217	5.28
8479		1.07	0.08	2.26	1815	140	1.88	2.92	2.89	0.02	25.9	1520	23	1.62	44.0	36.8
8480		0.97	0.13	2.34	3510	140	1.91	4.21	2.81	<0.02	15.80	2880	24	1.64	71.9	35.7
8481		0.07	>100	5.39	1705	360	0.71	18.30	0.28	13.05	18.95	103.0	34	1.61	>10000	3.65
8482		2.36	0.93	1.58	55.0	110	1.04	1.08	2.04	0.02	2.10	92.3	15	1.50	252	45.5
8483		1.17	0.30	1.40	60.0	110	0.82	0.42	1.50	0.04	18.60	56.5	36	0.57	164.5	11.05
8484		1.68	0.10	1.83	19.0	120	1.15	0.42	2.26	<0.02	35.7	40.5	25	1.41	53.9	40.3
8485		1.44	0.10	3.95	9.6	240	2.09	0.33	4.36	<0.02	73.1	39.9	51	2.06	27.3	21.6
8486		1.54	0.04	4.80	15.9	100	1.85	0.88	10.25	0.04	47.1	27.8	52	0.23	9.5	11.65
8487		2.66	0.09	3.53	15.4	170	2.37	0.99	7.61	0.07	52.3	44.1	40	1.55	5.7	21.8
8488		2.43	0.06	3.92	5.7	250	3.28	0.32	8.50	0.15	49.8	22.3	37	<0.05	3.9	10.25
8489		1.13	0.06	3.80	6.5	1100	3.93	0.24	8.16	0.04	41.2	19.7	32	0.11	10.3	10.45
8490		2.04	0.06	6.83	7.5	1430	2.40	0.31	0.60	0.03	156.5	7.8	10	0.38	16.2	1.29
8491		0.90	0.10	6.72	7.8	1520	2.55	0.26	0.41	0.03	171.0	5.0	13	0.49	11.3	1.24
8492		0.99	0.08	6.46	5.4	1010	3.40	0.06	0.31	0.03	82.8	2.2	13	0.37	7.8	0.71
8493		1.96	0.03	6.84	5.7	1580	2.49	0.14	0.43	0.06	177.5	4.4	14	0.46	4.7	1.25
8494		1.95	0.06	7.07	5.6	1620	2.05	0.08	0.56	0.04	196.5	4.2	14	0.64	11.7	1.68
8495		2.29	0.05	8.20	4.9	1930	1.89	0.07	0.44	0.04	219	4.3	11	1.48	10.9	2.62
8496		2.12	0.04	6.93	5.6	2220	2.36	0.07	0.70	0.07	183.5	4.8	14	0.51	12.8	1.34
8497		1.29	0.05	7.21	7.0	280	1.81	0.20	7.42	0.03	23.3	37.3	45	2.71	77.7	7.63
8498		1.39	0.07	6.80	4.8	2140	2.24	0.07	0.76	0.12	197.0	4.2	13	0.68	27.8	1.33
8499		2.27	0.03	7.54	4.3	1850	2.16	0.08	0.82	0.14	197.5	4.8	13	0.87	24.6	1.52
8500		2.05	0.04	7.12	4.3	1820	3.11	0.04	0.51	0.07	147.0	2.9	12	0.58	6.8	1.28
8501		2.06	0.02	7.13	2.8	1220	2.42	0.06	0.38	0.03	193.5	3.7	18	0.67	4.7	1.78
8502		2.15	0.06	6.83	3.8	1170	3.60	0.05	0.45	0.03	171.5	2.6	13	0.46	6.1	1.59
8503		1.52	0.03	7.17	3.4	1920	3.46	0.05	0.55	0.03	203	2.3	17	0.83	2.7	1.73
8504		1.71	0.04	7.40	4.3	920	2.26	0.06	0.37	0.04	208	8.3	15	0.88	7.1	2.16

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: BATTERY MINERAL RESOURCES LTD.
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 5-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18114878

Sample Description	Method / Analyte / Units / LOR	ME-MS61 Ga ppm 0.05	ME-MS61 Ge ppm 0.05	ME-MS61 Hf ppm 0.1	ME-MS61 In ppm 0.005	ME-MS61 K % 0.01	ME-MS61 La ppm 0.5	ME-MS61 Li ppm 0.2	ME-MS61 Mg % 0.01	ME-MS61 Mn ppm 5	ME-MS61 Mo ppm 0.05	ME-MS61 Na % 0.01	ME-MS61 Nb ppm 0.1	ME-MS61 Ni ppm 0.2	ME-MS61 P ppm 10	ME-MS61 Pb ppm 0.5
8465		18.60	0.18	4.6	0.258	4.01	48.5	22.8	2.38	1180	3.02	1.10	10.1	39.2	440	15.2
8466		13.70	0.17	4.3	0.149	4.76	28.0	9.7	1.24	821	1.57	1.05	9.0	33.8	400	11.0
8467		16.75	0.20	5.8	0.089	4.31	48.6	8.2	1.45	834	2.25	2.40	9.8	37.4	560	21.8
8468		16.70	0.21	6.6	0.053	4.61	56.6	10.0	1.00	506	1.41	2.24	11.0	27.3	520	23.6
8469		14.75	0.18	4.8	0.067	3.70	36.0	9.5	0.90	543	1.88	2.36	9.7	24.0	430	13.1
8470		17.45	0.88	1.3	0.183	0.86	10.6	11.3	3.53	824	0.24	0.04	2.8	9.5	90	6.3
8471		16.80	1.00	0.9	0.193	0.33	0.7	7.6	3.70	758	0.34	0.03	2.0	12.0	80	6.2
8472		20.9	1.13	1.1	0.246	0.62	0.8	9.6	4.02	773	0.20	0.05	1.9	8.5	90	8.4
8473		16.45	1.00	0.7	0.234	0.37	0.5	5.8	3.15	708	0.35	0.05	1.1	15.9	80	48.5
8474		15.75	0.23	2.8	0.314	2.60	18.6	32.8	7.24	1280	0.13	0.08	6.6	41.6	230	7.4
8475		0.26	0.10	<0.1	<0.005	0.01	1.2	1.2	1.34	85	0.07	0.03	0.1	0.6	60	<0.5
8476		10.20	0.08	2.6	0.232	1.58	27.7	35.2	5.97	2490	1.21	0.24	6.0	27.7	210	11.8
8477		10.80	0.08	2.4	0.256	1.57	35.2	19.5	5.10	2800	3.05	0.65	5.2	27.6	210	12.1
8478		13.10	0.12	3.6	0.128	3.99	50.7	4.6	0.66	470	9.39	1.73	8.7	27.0	310	24.9
8479		18.45	1.12	1.7	0.399	0.70	16.5	13.7	4.40	1160	0.22	0.25	4.6	14.5	150	4.3
8480		18.25	0.98	1.7	0.400	0.73	9.2	14.1	4.49	1150	0.42	0.23	4.3	17.5	160	4.1
8481		32.0	0.24	2.9	4.09	1.03	7.7	22.1	0.05	96	4.86	0.55	7.1	1550	510	1430
8482		18.95	1.05	1.2	0.235	0.65	1.1	11.4	3.81	889	0.44	0.05	2.8	11.5	140	6.1
8483		9.76	0.07	1.0	0.191	0.26	10.2	8.1	2.45	650	1.69	0.21	2.1	16.1	80	8.1
8484		17.50	1.18	1.7	0.405	0.62	21.0	13.4	3.64	996	0.28	0.09	3.6	20.3	120	5.0
8485		14.70	0.42	3.2	0.843	0.99	44.1	19.8	4.86	1840	0.07	0.67	7.1	37.2	260	5.1
8486		14.15	0.08	2.5	0.601	0.24	27.4	4.9	2.88	2940	0.12	0.82	8.2	36.4	290	15.9
8487		13.40	0.15	2.5	0.638	0.79	29.6	9.3	3.39	2310	0.15	0.64	6.7	37.5	240	20.5
8488		10.40	0.08	2.7	0.478	0.71	26.3	1.9	2.52	2330	0.95	1.56	6.3	29.7	190	23.5
8489		8.26	0.09	2.8	0.320	2.76	18.5	2.0	2.13	1700	2.04	0.80	6.9	25.7	200	20.6
8490		20.1	0.20	6.0	0.015	3.57	92.2	5.4	0.30	171	1.19	3.27	18.9	2.6	310	18.9
8491		19.70	0.22	6.4	0.015	3.76	98.9	7.3	0.33	147	2.34	3.06	16.9	2.4	320	17.3
8492		20.0	0.17	4.0	0.008	4.03	45.7	4.1	0.16	97	2.85	2.89	15.5	1.6	140	18.2
8493		19.75	0.21	6.8	0.020	3.76	100.5	8.9	0.38	161	1.92	3.18	21.4	3.2	350	23.9
8494		20.6	0.20	6.3	0.021	3.70	109.5	7.2	0.41	182	2.01	3.32	20.9	4.1	340	21.7
8495		24.5	0.23	9.0	0.013	4.21	121.0	13.6	0.81	290	0.64	3.57	27.6	3.6	390	22.7
8496		18.90	0.22	6.6	0.020	3.87	105.0	7.0	0.37	210	1.43	2.96	16.5	3.4	350	36.1
8497		16.30	0.10	2.0	0.090	1.60	9.4	16.0	3.60	1620	0.49	1.71	3.7	82.1	310	9.5
8498		19.55	0.22	6.6	0.024	3.99	115.0	6.7	0.32	243	1.44	2.75	16.9	2.7	350	45.2
8499		21.6	0.22	6.9	0.027	4.27	116.0	6.4	0.34	232	0.80	3.23	27.5	2.8	340	42.5
8500		21.2	0.19	6.6	0.013	4.24	81.0	6.9	0.34	165	1.62	2.84	18.7	2.6	330	32.3
8501		19.10	0.22	6.5	0.014	3.31	111.5	7.5	0.40	176	1.25	3.59	16.9	3.7	340	11.0
8502		19.35	0.22	6.4	0.017	3.20	100.5	5.4	0.28	152	1.86	3.56	23.3	2.9	290	14.8
8503		19.55	0.25	6.9	0.020	3.92	116.0	7.4	0.36	177	2.79	3.20	19.0	2.7	370	16.3
8504		19.40	0.24	6.7	0.013	2.99	120.0	7.8	0.46	195	1.77	3.98	17.0	5.2	360	12.7

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: BATTERY MINERAL RESOURCES LTD.
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 5-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18114878

Sample Description	Method / Analyte / Units / LOR	ME-MS61 Rb ppm 0.1	ME-MS61 Re ppm 0.002	ME-MS61 S % 0.01	ME-MS61 Sb ppm 0.05	ME-MS61 Sc ppm 0.1	ME-MS61 Se ppm 1	ME-MS61 Sn ppm 0.2	ME-MS61 Sr ppm 0.2	ME-MS61 Ta ppm 0.05	ME-MS61 Te ppm 0.05	ME-MS61 Th ppm 0.01	ME-MS61 Ti % 0.005	ME-MS61 Tl ppm 0.02	ME-MS61 U ppm 0.1	ME-MS61 V ppm 1
8465		209	0.004	0.27	0.41	10.4	<1	2.5	201	0.80	0.05	15.00	0.245	1.68	5.2	60
8466		133.0	0.004	0.40	0.47	7.4	1	1.8	73.3	0.71	0.08	18.10	0.192	0.95	5.1	49
8467		108.0	0.003	0.15	0.46	10.6	<1	1.9	67.0	0.84	0.09	19.25	0.272	0.71	5.8	71
8468		165.0	0.002	0.51	0.39	7.6	<1	2.0	56.6	0.89	<0.05	23.4	0.233	1.24	7.0	46
8469		123.5	0.002	0.11	0.33	7.1	<1	2.0	47.4	0.78	0.05	19.80	0.214	1.02	5.3	47
8470		66.8	<0.002	0.34	0.45	3.1	1	1.4	10.5	0.24	0.53	3.35	0.072	0.61	5.2	22
8471		28.1	<0.002	0.37	0.52	2.2	1	1.0	7.8	0.17	1.67	2.74	0.049	0.26	5.2	15
8472		50.9	<0.002	0.60	0.54	2.5	1	1.4	4.8	0.19	1.87	2.91	0.058	0.52	6.5	16
8473		29.8	<0.002	2.04	0.64	1.6	2	1.1	5.5	0.11	1.47	1.75	0.036	0.32	6.0	11
8474		214	0.003	0.25	0.49	7.2	<1	2.7	8.4	0.47	0.38	8.72	0.158	2.08	4.6	47
8475		0.8	<0.002	<0.01	0.09	0.2	1	<0.2	83.5	<0.05	<0.05	0.10	0.005	<0.02	0.2	1
8476		128.0	<0.002	0.44	0.47	5.7	<1	1.9	84.2	0.45	0.11	8.47	0.131	1.20	3.8	38
8477		118.5	<0.002	0.69	0.52	5.2	1	2.3	98.6	0.43	0.18	10.25	0.125	1.16	5.5	43
8478		89.8	0.005	0.12	0.40	5.6	1	2.3	29.1	0.61	<0.05	19.80	0.157	0.72	4.7	37
8479		52.6	0.002	0.13	0.55	4.2	1	2.6	10.6	0.32	2.46	4.91	0.091	0.46	8.2	27
8480		57.6	0.005	0.22	0.55	4.2	2	2.7	8.8	0.32	4.43	4.74	0.092	0.49	7.5	28
8481		32.1	0.002	8.38	308	5.1	80	3.0	347	0.57	35.8	3.59	0.178	16.35	2.7	39
8482		51.1	0.002	0.23	0.69	2.9	1	1.3	2.7	0.19	0.12	2.90	0.064	0.42	7.2	16
8483		19.2	0.002	0.41	0.40	2.5	1	1.0	5.4	0.18	0.13	2.57	0.055	0.17	2.7	17
8484		47.6	<0.002	0.14	0.60	4.1	<1	2.2	7.1	0.28	0.06	5.51	0.085	0.42	7.0	25
8485		70.4	<0.002	0.06	0.58	8.4	<1	4.2	30.8	0.57	0.08	10.55	0.175	0.61	3.2	53
8486		8.4	<0.002	0.03	1.04	8.4	1	3.9	91.8	0.63	0.06	10.30	0.197	0.08	3.2	54
8487		57.7	<0.002	0.08	0.85	6.3	<1	4.6	153.5	0.51	0.14	9.18	0.148	0.44	4.1	39
8488		14.4	<0.002	0.02	0.59	4.8	<1	4.0	128.5	0.48	<0.05	13.85	0.126	0.06	3.9	31
8489		63.8	<0.002	0.03	0.52	4.4	<1	2.6	109.0	0.53	<0.05	14.85	0.118	0.22	2.6	30
8490		118.0	0.002	0.18	0.26	4.2	<1	2.7	69.2	1.89	<0.05	62.4	0.166	0.49	10.7	13
8491		132.0	<0.002	0.13	0.25	3.9	<1	2.1	63.5	1.87	<0.05	68.7	0.166	0.55	11.6	13
8492		143.0	<0.002	0.04	0.20	4.2	<1	1.4	64.0	1.77	<0.05	45.6	0.081	0.59	7.7	6
8493		121.5	<0.002	0.06	0.27	4.3	<1	2.3	68.8	2.07	<0.05	68.6	0.177	0.52	14.7	16
8494		125.5	0.002	0.05	0.25	4.3	1	2.5	66.8	1.90	<0.05	75.5	0.175	0.63	14.7	18
8495		169.0	<0.002	0.05	0.24	5.4	<1	2.5	65.2	2.48	<0.05	99.6	0.241	0.98	24.3	24
8496		141.0	<0.002	0.05	0.26	4.0	<1	1.6	132.0	1.67	<0.05	80.3	0.181	0.68	13.7	16
8497		188.5	<0.002	0.07	0.67	34.0	1	1.3	417	0.33	<0.05	5.73	0.456	1.34	1.7	210
8498		181.5	<0.002	0.06	0.23	3.9	1	1.7	163.0	1.79	<0.05	78.0	0.177	0.98	14.5	15
8499		198.5	<0.002	0.06	0.24	4.7	1	2.7	185.5	3.47	<0.05	78.0	0.180	1.18	15.3	13
8500		197.0	<0.002	0.01	0.19	4.3	1	2.3	149.0	2.70	<0.05	74.6	0.170	0.99	18.9	15
8501		121.0	<0.002	0.03	0.15	3.8	1	2.0	74.1	1.69	<0.05	78.1	0.177	0.56	14.8	16
8502		108.0	<0.002	0.02	0.18	4.0	<1	2.0	79.6	3.43	<0.05	70.8	0.161	0.51	20.2	15
8503		146.0	<0.002	<0.01	0.18	4.1	1	2.2	109.5	1.85	<0.05	83.9	0.188	0.72	14.9	18
8504		123.0	<0.002	0.11	0.17	3.8	<1	1.6	65.2	1.81	<0.05	85.4	0.187	0.61	10.2	18

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: BATTERY MINERAL RESOURCES LTD.
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 5-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18114878

Sample Description	Method / Analyte / Units / LOR	ME-MS61 W ppm 0.1	ME-MS61 Y ppm 0.1	ME-MS61 Zn ppm 2	ME-MS61 Zr ppm 0.5	Ag-OG62 Ag ppm 1	Cu-OG62 Cu % 0.001	Ni-OG62 Ni % 0.001	CRU-QC Pass2mm % 0.01	PUL-QC Pass75um % 0.01
8465		0.8	23.1	173	165.0					
8466		0.7	17.6	69	157.0					
8467		1.3	22.6	101	202					
8468		0.7	20.8	65	230					
8469		0.5	16.8	56	166.5					
8470		0.2	6.3	110	44.8					
8471		0.2	3.2	103	32.5					
8472		0.2	4.2	118	42.3					
8473		0.2	4.1	93	26.7					
8474		0.3	11.2	211	98.9					
8475		0.1	1.8	3	1.7					
8476		0.3	12.3	172	91.8					
8477		0.3	11.3	182	84.4					
8478		0.4	13.5	36	123.0					
8479		0.2	10.3	116	61.9					
8480		0.2	10.6	117	64.7					
8481		30.1	4.5	2230	97.3	996	5.04			
8482		0.2	4.2	99	43.1					
8483		0.2	4.8	67	36.1					
8484		0.2	9.4	96	60.1					
8485		0.1	17.8	137	114.0					
8486		0.2	16.4	93	89.2					
8487		0.2	10.8	134	89.5					
8488		0.3	15.1	134	95.0					
8489		0.3	16.2	84	103.0					
8490		0.2	19.7	25	216					
8491		0.3	20.0	23	230					
8492		0.2	19.4	15	123.0				81.3	
8493		0.3	22.0	25	244					
8494		0.2	21.4	28	239					
8495		0.2	24.1	48	336					
8496		0.2	14.1	27	247					
8497		0.4	15.6	104	69.0					
8498		0.2	14.8	35	251					
8499		0.2	22.2	35	250					
8500		0.3	20.0	29	237					
8501		0.3	15.4	22	246					
8502		0.3	23.0	20	222					
8503		0.4	20.2	25	272					
8504		0.2	13.7	27	260				82.8	90.3

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: BATTERY MINERAL RESOURCES LTD.
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 5-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18114878

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	ME-MS61 Ag ppm 0.01	ME-MS61 Al % 0.01	ME-MS61 As ppm 0.2	ME-MS61 Ba ppm 10	ME-MS61 Be ppm 0.05	ME-MS61 Bi ppm 0.01	ME-MS61 Ca % 0.01	ME-MS61 Cd ppm 0.02	ME-MS61 Ce ppm 0.01	ME-MS61 Co ppm 0.1	ME-MS61 Cr ppm 1	ME-MS61 Cs ppm 0.05	ME-MS61 Cu ppm 0.2	ME-MS61 Fe % 0.01
8505		2.26	0.04	6.93	4.5	70	1.91	0.05	1.86	0.03	160.0	8.4	14	0.15	13.0	1.89
8506		2.43	0.05	7.19	7.3	390	1.93	0.15	4.79	0.02	16.35	35.3	58	4.42	86.8	8.15
8507		2.42	0.08	7.25	3.4	330	0.82	0.12	6.24	0.10	19.45	48.9	49	2.29	143.0	8.24
8508		2.54	0.07	7.46	5.8	140	0.44	0.05	6.87	0.09	18.30	51.0	38	1.11	127.0	8.60
8509		2.43	0.09	7.56	2.5	150	0.51	0.07	6.90	0.09	22.0	48.4	57	1.11	149.5	8.28
8510		2.40	0.09	7.80	16.6	50	0.51	0.18	7.05	0.13	29.5	49.5	29	0.09	85.2	8.47
8511		2.32	0.13	6.97	1.9	170	0.57	0.11	6.54	0.11	20.7	60.2	7	1.16	190.0	10.55
8512		2.57	0.14	6.25	3.6	430	0.79	0.17	5.23	0.22	31.9	61.1	3	1.42	176.5	13.65
8513		2.43	0.05	6.17	2.6	360	1.38	0.14	3.97	0.12	56.0	44.5	2	1.05	55.8	12.25
8514		2.45	0.06	6.08	2.7	400	1.19	0.15	4.15	0.15	48.8	49.7	3	1.22	60.1	13.15
8515		2.47	0.08	6.05	3.8	300	0.91	0.19	4.76	0.18	39.0	60.1	3	0.81	78.8	13.05
8516		2.39	0.50	6.38	1.8	130	1.08	1.62	5.86	0.46	39.1	114.0	1	0.46	281	13.10
8517		2.55	0.13	6.13	3.0	290	0.81	0.17	4.94	0.15	32.3	65.8	1	1.41	131.0	14.30

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: BATTERY MINERAL RESOURCES LTD.
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 5-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18114878

Sample Description	Method / Analyte / Units / LOR	ME-MS61 Ga ppm 0.05	ME-MS61 Ge ppm 0.05	ME-MS61 Hf ppm 0.1	ME-MS61 In ppm 0.005	ME-MS61 K % 0.01	ME-MS61 La ppm 0.5	ME-MS61 Li ppm 0.2	ME-MS61 Mg % 0.01	ME-MS61 Mn ppm 5	ME-MS61 Mo ppm 0.05	ME-MS61 Na % 0.01	ME-MS61 Nb ppm 0.1	ME-MS61 Ni ppm 0.2	ME-MS61 P ppm 10	ME-MS61 Pb ppm 0.5
8505		20.7	0.21	6.4	0.011	0.25	89.9	4.8	0.38	252	1.39	5.38	17.2	4.7	350	8.4
8506		19.75	0.11	1.4	0.050	2.39	7.4	27.1	3.42	1150	2.46	2.14	4.4	75.1	320	5.9
8507		16.25	0.10	1.8	0.070	1.40	8.2	17.4	3.73	1340	0.48	1.38	3.2	89.6	360	9.0
8508		16.30	0.10	1.6	0.066	0.60	7.7	8.3	3.84	1420	0.53	1.64	3.0	81.8	330	8.0
8509		16.85	0.09	2.0	0.064	0.62	9.4	8.0	3.67	1360	0.62	1.71	3.6	81.7	380	5.5
8510		21.5	0.09	2.0	0.105	0.19	14.3	7.4	2.65	1250	0.84	2.31	4.1	55.2	430	10.8
8511		18.25	0.08	1.8	0.078	0.68	8.9	9.7	3.15	1620	0.57	1.69	3.5	49.8	360	6.1
8512		21.3	0.10	2.7	0.103	1.13	15.4	12.2	2.18	1980	1.85	1.67	5.5	23.4	510	8.1
8513		22.2	0.11	4.8	0.124	0.95	27.2	8.5	1.04	1640	1.32	2.35	9.4	1.3	900	7.8
8514		21.4	0.10	4.5	0.114	1.07	23.1	9.4	1.20	1850	1.17	2.01	8.5	1.2	850	8.3
8515		21.0	0.09	3.7	0.111	1.01	17.8	8.7	1.50	1820	1.01	1.84	6.6	4.4	650	8.9
8516		20.7	0.09	3.5	0.308	0.50	17.0	6.8	1.77	1670	0.82	3.09	6.7	21.4	580	7.9
8517		21.1	0.09	3.0	0.104	0.96	15.0	9.6	1.90	1800	0.75	1.81	5.7	15.9	560	6.1

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 5-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18114878

Sample Description	Method / Analyte / Units / LOR	ME-MS61 Rb ppm 0.1	ME-MS61 Re ppm 0.002	ME-MS61 S % 0.01	ME-MS61 Sb ppm 0.05	ME-MS61 Sc ppm 0.1	ME-MS61 Se ppm 1	ME-MS61 Sn ppm 0.2	ME-MS61 Sr ppm 0.2	ME-MS61 Ta ppm 0.05	ME-MS61 Te ppm 0.05	ME-MS61 Th ppm 0.01	ME-MS61 Ti % 0.005	ME-MS61 Tl ppm 0.02	ME-MS61 U ppm 0.1	ME-MS61 V ppm 1
8505		9.9	<0.002	0.10	0.14	3.6	1	1.8	47.2	2.06	<0.05	76.0	0.172	0.08	10.9	21
8506		165.5	<0.002	0.04	0.27	32.6	1	1.2	209	0.28	<0.05	2.36	0.514	1.72	1.7	225
8507		127.0	<0.002	0.10	0.36	37.7	1	0.9	214	0.24	<0.05	2.27	0.516	0.92	0.6	241
8508		33.7	0.002	0.07	0.29	38.9	1	0.7	199.5	0.22	<0.05	2.03	0.508	0.27	0.6	249
8509		32.8	0.002	0.09	0.28	37.1	1	0.9	211	0.26	<0.05	2.58	0.555	0.25	0.8	251
8510		7.6	<0.002	0.05	0.60	38.3	1	1.1	292	0.30	<0.05	2.94	0.634	0.07	1.0	291
8511		35.9	0.002	0.12	0.31	42.3	1	0.9	201	0.26	<0.05	2.28	0.846	0.27	0.7	438
8512		54.6	0.006	0.11	0.42	43.7	1	1.5	182.0	0.41	<0.05	3.70	1.315	0.36	1.1	632
8513		34.5	0.003	0.16	0.34	33.6	1	1.8	161.5	0.66	<0.05	6.52	1.070	0.21	1.9	89
8514		39.0	0.002	0.18	0.33	34.0	1	1.7	170.0	0.63	<0.05	6.12	1.120	0.23	1.7	94
8515		39.2	0.006	0.22	0.48	39.6	1	1.5	188.0	0.48	<0.05	4.63	1.295	0.20	1.3	281
8516		14.8	0.006	1.25	0.39	40.1	2	2.9	130.5	0.49	0.83	4.49	1.530	0.27	3.0	452
8517		46.7	0.004	0.16	0.38	43.0	1	1.3	174.0	0.43	<0.05	3.67	1.495	0.28	1.1	658

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: BATTERY MINERAL RESOURCES LTD.
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 5-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18114878

Sample Description	Method / Analyte / Units / LOR	ME-MS61 W ppm 0.1	ME-MS61 Y ppm 0.1	ME-MS61 Zn ppm 2	ME-MS61 Zr ppm 0.5	Ag-OG62 Ag ppm 1	Cu-OG62 Cu % 0.001	Ni-OG62 Ni % 0.001	CRU-QC Pass2mm % 0.01	PUL-QC Pass75um % 0.01
8505		0.2	13.8	21	247					
8506		0.4	14.4	109	51.1					
8507		0.4	18.2	108	56.5					
8508		0.3	17.3	106	59.7					
8509		0.3	18.7	100	73.7					
8510		0.6	23.4	101	76.7					
8511		0.4	18.1	130	62.2					
8512		0.7	26.6	215	101.0					
8513		0.7	40.8	153	178.5					
8514		0.7	37.6	169	166.0					
8515		0.7	30.9	207	131.0					
8516		0.9	38.9	251	134.0					
8517		0.5	26.9	163	109.5					

***** See Appendix Page for comments regarding this certificate *****

ALS Canada Ltd.
2103 Dollarton Hwy
North Vancouver BC V7H 0A7
Phone: +1 (604) 984 0221 Fax: +1 (604) 984 0218
www.alsglobal.com/geochemistry

To: **BATTERY MINERAL RESOURCES LTD.**
207 – 744 WEST HASTINGS STREET
VANCOUVER BC V6C 1A5

Finalized Date: 5-JUN-2018
Account: BMRPLLBW

Project: IRON MASK

CERTIFICATE OF ANALYSIS SD18114878

CERTIFICATE COMMENTS

ANALYTICAL COMMENTS

REE's may not be totally soluble in this method.

Applies to Method: ME-MS61

LABORATORY ADDRESSES

Processed at ALS Sudbury located at 1351-B Kelly Lake Road, Unit #1, Sudbury, ON, Canada.

Applies to Method:

CRU-31	CRU-QC	LOG-22	LOG-24
PUL-31	PUL-QC	SPL-21	WEI-21

Processed at ALS Vancouver located at 2103 Dollarton Hwy, North Vancouver, BC, Canada.

Applies to Method:

Ag-OG62	Cu-OG62	ME-MS61	ME-OG62
Ni-OG62			