



41104SE0002 0015 KILLARNEY

010

This Report (2.9120) is an assay analysis of samples taken as part of previous reports.

The following two pages are part of Reports: DD12 and DD13 which have been filmed. Please see: Killarney-0013-A1 and Killarney-0014-A1 for more information regarding those reports.

DIAPHRAGM LOGGING

TOWNSHIP:
KILLARNEY

REPORT NO.: 12*

WORK PERFORMED BY:

<u>CLAIM No.</u>	<u>HOLE No.</u>	<u>FOOTAGE</u>	<u>DATE</u>	<u>NOTE</u>
S 626354	A-1	500	June/83	(1)
626359	A-2	351	June/83	(1)
	A-3	402	July/83	(1)
	A-4	200	July/83	(1)
	B-1	477	June/83	(1)
S 626360	B-2	251	June/83	(1)
626361	B-3	250	July/83	(1)
<u>TOTAL 7 DH</u>		<u>2431 FT</u>		

NOTES: (1) '02-83

* PREVIOUSLY FILMED
FOR MORE INFORMATION
PLEASE SEE
FICHE #: KILLARNEY-0013-A1

Diamond Drilling

Township KILLARNEY

Report NO 13 *

Work performed by: INDISMIN LTD.

Claim NO	Hole NO	Footage	Date	Note
S 626361	85-1-4	592'	May-June/85	(1)
	85-B-5	573'	June/85	(1)
S 621362	85-C-1	652'	May-June/85	(1)
TOTAL	3 DM	1817 FT		

* PREVIOUSLY FILMED
FOR MORE INFORMATION
PLEASE SEE
FICHE: KILLARNEY-0014-A1

Notes: (1) 85-65

SAMPLE NO.	FROM	TO	LENGTH	ASSAYS %										DESCRIPTION
				-30 Crude					-30 +200					
				Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	
415	150.0'	160.0'	10.0'	.020	.33	.01	<.01	.033	.013	.27	<.01	<.01	.028	
416	160.0'	170.0'	10.0'	.022	.31	<.01	<.01	.031	.011	.26	<.01	<.01	.027	
417	170.0'	182.9'	12.9'	.017	.26	.08	<.01	.025	<.01	.22	.08	<.01	.021	
418	182.9'	190.0'	7.1'	.016	.25	.06	<.01	.026	<.01	.19	.06	<.01	.020	
419	190.0'	200.0'	10.0'	.018	.34	.02	<.01	.033	<.01	.27	.01	<.01	.026	
420	200.0'	204.2'	4.2'	.030	.78	.02	<.01	.049	.023	.68	.02	<.01	.046	
421	204.2'	209.3'	5.1'	.014	.26	.94	.01	.021	<.01	.22	1.05	<.01	.019	
422	209.3'	220.0'	10.7'	<.01	.36	.02	<.01	.027	<.01	.33	.02	<.01	.028	
423	220.0'	232.5'	12.5'	.015	.43	<.01	<.01	.036	<.01	.37	<.01	<.01	.031	
424	232.5'	240.0'	7.5'	.031	.99	<.01	<.01	.054	.017	.86	<.01	<.01	.047	
425	240.0'	250.0'	10.0'	.014	.50	.02	<.01	.038	<.01	.44	.02	<.01	.030	
426	250.0'	260.0'	10.0'	.014	.38	<.01	<.01	.031	<.01	.33	<.01	<.01	.028	
427	260.0'	270.0'	10.0'	.018	.25	<.01	<.01	.024	.012	.22	<.01	<.01	.020	
428	270.0'	280.0'	10.0'	.022	.30	<.01	<.01	.029	.022	.27	<.01	<.01	.022	
429	280.0'	290.0'	10.0'	.01	.33	<.01	<.01	.033	<.01	.28	<.01	<.01	.027	

INDUSMIN LIMITED

PROPERTY FRASER BAY HILL

SAMPLE RECORD

SAMPLE NO.	FROM	TO	LENGTH	ASSAYS %										DESCRIPTION
				-30 Crude					-30 +200					
				Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	SiO ₂	Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	
445	430.0'	440.0'	10.0'	.022	.26	<.01	<.01	.033	.011	.24	<.01	<.01	.029	
446	440.0'	450.0'	10.0'	.033	1.84	.01	<.01	.098	.025	1.76	<.01	<.01	.089	
447	450.0'	460.0'	10.0'	.052	1.77	.02	<.01	.094	.039	1.59	.01	<.01	.079	
448	460.0'	470.0'	10.0'	.017	.25	<.01	<.01	.033	.01	.22	<.01	<.01	.032	
449	470.0'	480.0'	10.0'	.020	.24	<.01	<.01	.037	.01	.22	<.01	<.01	.033	
450	480.0'	490.0'	10.0'	.014	.25	<.01	<.01	.032	.01	.22	<.01	<.01	.030	
451	490.0'	500.0'	10.0'	.016	.25	<.01	<.01	.031	.011	.23	<.01	<.01	.031	

RECEIVED
 JUN 11 1961
 INDUSTRIAL DIV.

INDUSMIN LIMITED

PROPERTY FRAZER BAY HILL

SAMPLE RECORD

SAMPLE NO.	FROM	TO	LENGTH	-30 Crude ASSAYS & -30 +200										DESCRIPTION
				Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	
348	5.0'	15.0'	10.0	.027	.43	<.01	<.01	.043	.024	.41	<.01	.01	.044	
349	15.0	25.0	10.0	.015	.28	<.01	<.01	.032	.013	.29	<.01	.01	.029	
350	25.0	35.0	10.0	.013	.22	<.01	.01	.033	.011	.24	<.01	<.01	.028	
351	35.0	45.0	10.0	.011	.19	.01	<.01	.025	.011	.19	<.01	<.01	.025	
352	45.0	55.0	10.0	.013	.21	<.01	<.01	.026	.014	.21	<.01	.01	.028	
353	55.0	65.0	10.0	.015	.27	<.01	<.01	.031	.013	.28	<.01	<.01	.033	
354	65.0	75.0	10.0	.015	.30	<.01	<.01	.038	.013	.30	<.01	<.01	.037	
355	75.0	85.0	10.0	.013	.32	<.01	<.01	.035	.012	.32	<.01	<.01	.037	
356	85.0	95.0	10.0	.016	.43	.01	<.01	.043	.018	.44	.01	<.01	.043	
357	95.0	105.0	10.0	.010	.32	.02	<.01	.042	.010	.32	.02	<.01	.038	
358	105.0	115.0	10.0	<.01	.26	.01	<.01	.035	<.01	.28	.01	<.01	.035	
359	115.0	120.9	5.9	<.01	.23	.01	.01	.029	<.01	.24	.01	<.01	.027	
360	122.8	124.0	1.2	.092	2.68	.02	.02	.121	.093	2.65	.02	.02	.119	120.9'-122.8-1.9' Sericite Schist not sampled
361	124.0	135.0	11.0	.031	.84	.01	.01	.060	.028	.80	.01	<.01	.058	
362	135.0	145.0	10.0	<.01	.28	.01	<.01	.033	<.01	.28	.02	.02	.032	

RECEIVED
 JUN 1968
 1968 JUN 19 1968

SAMPLE NO.	FROM	TO	LENGTH	-30 Crude ASSAYS % -30 +20C										DESCRIPTION
				Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	
363	145.0'	155.0'	10.0	.036	.47	<.01	<.01	.046	.035	.50	<.01	<.01	.045	
364	155.0	165.0	10.0	<.01	.28	<.01	<.01	.032	<.01	.25	<.01	<.01	.029	
365	165.0	175.0	10.0	<.01	.17	<.01	<.01	.022	<.01	.16	<.01	<.01	.020	
366	175.0	185.0	10.0	<.01	.23	<.01	<.01	.028	<.01	.22	<.01	<.01	.027	
367	185.0	195.0	10.0	<.01	.24	.01	<.01	.027	<.01	.24	<.01	<.01	.025	
368	195.0	205.0	10.0	<.01	.40	.01	<.01	.040	<.01	.40	.01	<.01	.035	
369	205.0	215.0	10.0	<.01	.32	.01	<.01	.034	<.01	.32	.01	<.01	.033	
370	215.0	225.0	10.0	<.01	.21	.01	<.01	.026	<.01	.21	.01	<.01	.024	
371	225.0	231.9	6.9	<.01	.42	.01	<.01	.038	<.01	.45	.01	<.01	.034	
372	231.9	237.7	5.8	.109	4.22	.02	.01	.143	.107	4.10	.01	.02	.137	
373	237.7	245.0	7.3	<.01	.27	<.01	<.01	.029	<.01	.26	<.01	<.01	.029	
374	245.0	255.0	10.0	.019	.28	<.01	<.01	.035	.019	.28	<.01	<.01	.038	
375	255.0	265.0	10.0	.016	.21	<.01	<.01	.031	.014	.21	<.01	<.01	.028	
376	265.0	277.0	12.0	.014	.22	.02	<.01	.036	.013	.23	.02	<.01	.036	
377	277.0	283.8	6.8	.145	.18	.03	.05	.032	.154	.19	.03	.06	.034	

RECEIVED
 1964

INDUSMIN LIMITED

SAMPLE RECORD

PROPERTY

SAMPLE NO.	FROM	TO	LENGTH	ASSAYS										DESCRIPTION
				-30 Crude					-30 +200					
				Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	
378	286.5	291.4	4.9	.819	.71	.05	.33	.089	.858	.76	.05	.40	.091	283.8' - 286.5' - 2.7' amphibolite dyke
379	291.4	300.0	8.6	.075	1.35	<.01	.04	.089	.079	1.47	<.01	.03	.087	
380	300.0	310.0	10.0	.048	1.54	<.01	.03	.133	.048	1.55	<.01	.02	.133	
381	310.0	320.0	10.0	<.01	.35	<.01	.01	.040	<.01	.36	.02	.01	.039	
382	320.0	330.0	10.0	<.01	.41	<.01	.02	.046	.011	.43	<.01	<.01	.047	
383	330.0	340.0	10.0	.015	.34	.01	.02	.039	.013	.34	.02	<.01	.040	
384	340.0	350.0	10.0	.017	.33	<.01	.03	.038	.014	.34	<.01	<.01	.036	
385	350.0	360.0	10.0	.014	1.37	<.01	.03	.075	.015	1.46	<.01	<.01	.077	
386	360.0	370.0	10.0	.016	.38	<.01	.02	.047	.017	.40	<.01	<.01	.046	
387	370.0	380.0	10.0	.014	.57	<.01	.03	.036	.014	.58	<.01	<.01	.057	
388	380.0	390.0	10.0	<.01	.36	.02	.03	.036	<.01	.38	.01	.02	.040	
389	390.0	401.0	11.0	.016	.54	<.01	.02	.046	.016	.61	<.01	.01	.051	
390	402.5	410.0	7.5	.043	1.52	<.01	.02	.096	.043	1.50	<.01	<.01	.092	401.0-4025'-1.5 Sericite Schist not sampled
391	410.0	420.0	10.0	.013	.44	<.01	.02	.042	.012	.41	<.01	<.01	.035	
392	420.0	430.0	10.0	<.01	.35	<.01	<.01	.039	<.01	.33	<.01	<.01	.039	

RECEIVED
APR 14 1964

INDUSMIN LIMITED
SAMPLE RECORD

PROPERTY FRAZER BAY HILL

SAMPLE NO.	FROM	TO	LENGTH	-30 Crude ASSAYS % -30 +200										DESCRIPTION
				Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	
398	2.0	10.0	8.0	.012	0.25	<.01	<.01	.032	.011	0.25	<.01	<.01	.031	
399	10.0	17.0	7.0	<.01	0.27	<.01	<.01	.031	<.01	0.27	<.01	<.01	.031	
400	17.0	23.0	6.0	.015	0.32	<.01	<.01	.028	<.01	0.26	<.01	<.01	.024	
501	23.0	30.0	7.0	<.01	0.30	<.01	<.01	.031		0.28	<.01	<.01	.029	
502	30.0	40.0	10.0	<.01	0.41	<.01	<.01	.036	<.01	0.40	<.01	<.01	.036	
503	40.0	50.0	10.0	<.01	0.60	<.01	.02	.097	<.01	0.57	<.01	<.01	.042	
504	50.0	60.0	10.0											Sample lost
505	60.0	70.0	10.0	<.01	0.32	<.01	.02	.034	<.01	0.32	<.01	<.01	.031	
506	70.0	80.0	10.0	<.01	0.47	<.01	<.01	.047	<.01	0.44	<.01	<.01	.042	
507	80.0	90.0	10.0	.012	0.42	<.01	<.01	.045	<.01	0.39	<.01	<.01	.038	
508	90.0	100.0	10.0	<.01	0.52	<.01	<.01	.044	<.01	0.50	<.01	<.01	.039	
509	100.0	110.0	10.0	<.01	0.42	<.01	<.01	.032	<.01	0.39	<.01	<.01	.030	
510	110.0	120.0	10.0	<.01	0.26	.01	.01	.035	<.01	0.24	.01	.01	.034	
511	120.0	125.0	5.0	<.01	0.36	.01	.01	.045	<.01	0.33	.01	.01	.041	
512	125.0	135.0	10.0	<.01	0.26	<.01	.01	.031	<.01	0.24	<.01	<.01	.031	

RECEIVED
 1957-10-10
 10:10 AM

INDUSMIN LIMITED
SAMPLE RECORD

PROPERTY FRAZER BAY HILL

SAMPLE NO.	FROM	TO	LENGTH	-30 Crude ASSAYS % -30 +200										DESCRIPTION
				Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	
513	135.0'	145.0'	10.0	<.01	0.37	<.01	<.01	.039	<.01	0.36	<.01	<.01	.035	
514	145.0	150.0	5.0	<.01	0.32	<.01	<.01	.038	<.01	0.34	<.01	<.01	.035	
515	150.0	151.5	1.5	<.01	0.24	<.01	<.01	.022	<.01	0.21	<.01	<.01	.022	
516	151.5	160.0	8.5	<.01	0.45	<.01	<.01	.043	<.01	0.44	<.01	<.01	.039	
517	160.0	170.0	10.0	.011	1.24	<.01	<.01	.069	.010	1.26	<.01	<.01	.065	
518	170.0	180.0	10.0	<.01	0.43	<.01	<.01	.041	<.01	0.42	<.01	<.01	.039	
519	180.0	190.0	10.0	<.01	0.47	<.01	<.01	.050	<.01	0.44	<.01	<.01	.041	
520	190.0	200.0	10.0	.013	0.71	<.01	<.01	.066	.010	0.71	<.01	<.01	.059	
521	200.0	204.7	4.7	.020	0.39	<.01	.01	.058	.016	0.39	<.01	.01	.053	
522	204.7	207.0	2.3	.553	0.30	.01	.04	.049	.552	0.29	.02	.04	.050	207.0' to 218.0'-11.0' diabase dy
523	218.0	230.0	12.0	.029	0.35	<.01	<.01	.045	.025	0.33	<.01	<.01	.045	
524	230.0	240.0	10.0	.027	1.34	<.01	<.01	.070	.019	1.26	<.01	<.01	.067	
525	240.0	251.0	11.0	.023	1.31	<.01	.02	.080	.020	1.19	<.01	<.01	.070	

RECEIVED
MAY 12 1956

INDUSMIN LIMITED

PROPERTY FRAZER BAY HILL

SAMPLE RECORD

SAMPLE NO.	FROM	TO	LENGTH	-30 Crude ASSAYS % -30 +200										DESCRIPTION
				Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	
526	2.0	9.5	7.5	.134	1.16	<.01	.02	.063	.121	1.04	<.01	.02	.059	
527	9.5	11.0	1.5	.404	6.19	<.01	.09	.295	.387	6.04	<.01	.12	.285	
528	11.0	21.0	10.0	.037	0.48	<.01	<.01	.038	.035	0.45	<.01	<.01	.035	
529	21.0	31.0	10.0	.023	0.34	<.01	<.01	.039	.020	0.32	<.01	<.01	.039	
530	31.0	41.0	10.0	.020	0.31	<.01	<.01	.036	.018	0.28	<.01	<.01	.033	
531	41.0	51.0	10.0	.022	0.40	<.01	<.01	.042	.018	0.39	<.01	<.01	.038	
532	51.0	61.0	10.0	.014	0.32	<.01	<.01	.039	.012	0.30	<.01	<.01	.038	
533	61.0	67.0	6.0	.035	1.53	<.01	<.01	.072	.032	1.54	<.01	<.01	.069	
534	67.0	73.0	6.0	.262	15.1	<.01	.07	.548	.248	14.4	<.01	.07	.513	
535	73.0	79.0	6.0	.101	6.01	<.01	.01	.231	.094	5.73	<.01	.02	.205	
536	79.0	90.0	11.0	.011	0.83	<.01	<.01	.058	.010	0.76	<.01	<.01	.052	
537	90.0	100.0	10.0	.013	0.48	<.01	<.01	.048	.012	0.44	<.01	<.01	.040	
538	100.0	110.0	10.0	.011	0.45	<.01	<.01	.044	<.01	0.44	<.01	<.01	.043	
539	110.0	120.0	10.0	<.01	0.48	<.01	<.01	.048	<.01	0.47	<.01	<.01	.049	
540	120.0	130.0	10.0	<.01	0.39	<.01	<.01	.037	<.01	0.39	<.01	<.01	.037	
541	130.0	140.0	10.0	.018	1.45	<.01	<.01	.101	.015	1.50	<.01	<.01	.098	

SECURITY
 RECEIVED
 JUN 11 1964
 11 13 11 23 45

INDUSMIN LIMITED

PROPERTY FRAZER BAY HILL

SAMPLE RECORD

SAMPLE NO.	FROM	TO	LENGTH	-30 Crude					ASSAYS					DESCRIPTION
				Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	
542	140.0	146.5	6.5	.010	0.83	<.01	<.01	.063	<.01	0.89	<.01	<.01	.064	
543	146.5	150.0	3.5											Sample missing
544	150.0	160.0	10.0	.017	0.24	<.01	<.01	.027	.014	0.22	<.01	<.01	.025	
545	160.0	170.0	10.0	.020	0.34	<.01	<.01	.041	.017	0.35	<.01	<.01	.042	
546	170.0	174.6	4.6	.014	0.15	<.01	<.01	.031	.011	0.19	<.01	<.01	.031	
547	174.6	180.0	5.4	.090	0.23	<.01	<.01	.035	.084	0.21	<.01	<.01	.035	
548	180.0	190.0	10.0	.040	0.28	<.01	<.01	.033	.036	0.27	<.01	<.01	.032	
549	190.0	198.6	8.6	.098	0.71	<.01	<.01	.051	.089	0.68	<.01	<.01	.049	
550	198.6	210.0	11.4	<.01	0.37	<.01	<.01	.039	<.01	0.35	<.01	<.01	.037	
551	210.0	220.0	10.0	<.01	0.31	<.01	<.01	.038	<.01	0.29	<.01	<.01	.037	
552	220.0	230.0	10.0	<.01	0.30	<.01	<.01	.038	<.01	0.29	<.01	<.01	.033	
553	230.0	240.0	10.0	<.01	0.47	<.01	<.01	.045	<.01	0.44	<.01	<.01	.041	
554	240.0	250.0	10.0	.015	1.42	<.01	<.01	.070	.015	1.40	<.01	<.01	.067	

RECEIVED
SECRETARY
INDUSMIN LIMITED
FRAZER BAY HILL
A.M.
1964

INDUSMIN LIMITED

PROPERTY: Fraser Bay Hill

SAMPLE RECORD

SAMPLE NO.	FROM	TO	LENGTH	ASSAYS										DESCRIPTION
				-30 Crude					-30 +200 Product					
				Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	
272	0.0'	10.0'	10.0'	.045	0.51	<0.01	<0.01	.042	.041	0.45	<0.01	<0.01	.039	
273	10.0'	18.0'	8.0'	.031	0.57	<0.01	<0.01	.050	.026	0.53	<0.01	<0.01	.046	
274	18.0'	25.0'	7.0'	.038	0.63	<0.01	<0.01	.053	.032	0.57	<0.01	<0.01	.055	
275	25.0'	37.0'	12.0'	.027	0.57	<0.01	<0.01	.049	.027	0.56	<0.01	<0.01	.048	
276	37.0'	45.0'	8.0'	.025	0.41	<0.01	<0.01	.045	.018	0.38	<0.01	<0.01	.038	
277	45.0'	55.0'	10.0'	.035	0.98	<0.01	<0.01	.084	.031	0.81	<0.01	<0.01	.070	
278	55.0'	65.0'	10.0'	.024	0.37	<0.01	<0.01	.038	.019	0.31	<0.01	<0.01	.030	
279	65.0	76.3'	11.3'	.025	0.39	<0.01	<0.01	.036	.024	0.34	<0.01	<0.01	.031	
280	76.3'	85.0'	8.7'	.039	0.95	<0.01	<0.01	.068	.029	0.84	<0.01	<0.01	.062	
281	85.0'	95.0'	10.0'	.035	0.89	<0.01	<0.01	.060	.029	0.70	<0.01	<0.01	.054	
282	95.0'	105.0'	10.0'	.021	0.51	<0.01	<0.01	.047	.017	0.44	<0.01	<0.01	.039	
283	105.0'	115.0'	10.0'	.028	0.63	<0.01	<0.01	.049	.024	0.61	<0.01	<0.01	.044	
284	115.0'	125.0'	10.0'	.044	1.03	<0.01	<0.01	.058	.038	1.03	<0.01	<0.01	.065	
285	125.0'	135.0'	10.0'	.013	0.39	<0.01	<0.01	.036	.015	0.31	<0.01	<0.01	.030	

RECEIVED
MAY 7 - 1985
MAY 11 1985

INDUSMIN LIMITED

PROPERTY Fraser Bay Hill

SAMPLE RECORD

SAMPLE NO.	FROM	TO	LENGTH	ASSAYS										DESCRIPTION
				-30 Crude					-30 +200 Product					
				Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	
286	135.0'	145.0'	10.0'	.022	0.42	<0.01	<0.01	.051	.019	0.39	<0.01	<0.01	.044	
287	145.0'	150.1'	5.1'	.025	0.44	<0.01	<0.01	.058	.023	0.38	<0.01	<0.01	.047	
288	150.0'	152.2'	2.4'	.175	0.34	<0.01	<0.01	.047	.158	0.29	<0.01	<0.01	.040	
	152.5'	154.8'	2.3'	-	-	-	-	-	-	-	-	-	-	Lamprophyre dyke
289	154.8'	156.2'	1.4'	.846	1.51	<0.01	<0.04	.084	.810	1.37	<0.01	<0.04	.077	
290	156.2'	159.5'	3.3'	.078	0.56	<0.01	<0.02	.028	.061	0.46	<0.01	<0.03	.025	
291	159.5'	169.0'	9.5'	1.340	13.30	<0.03	<0.27	.597	1.270	12.00	<0.02	<0.26	.548	
292	169.0'	180.0'	11.0'	.065	0.75	<0.01	<0.01	.054	.030	0.44	<0.01	<0.01	.037	
293	180.0'	190.0'	10.0'	.024	0.53	<0.01	<0.01	.057	.017	0.45	<0.01	<0.01	.049	
294	190.0'	200.0'	10.0'	.032	0.88	<0.01	<0.01	.099	.025	0.80	<0.01	<0.01	.093	
295	200.0'	210.0'	10.0'	.025	0.56	<0.01	<0.01	.056	.021	0.62	<0.01	<0.01	.054	
296	210.0'	220.0'	10.0'	.014	0.41	<0.01	<0.01	.046	<.010	0.39	<0.01	<0.01	.037	
297	220.0'	230.0'	10.0'	.016	0.48	<0.01	<0.01	.047	.012	0.35	<0.01	<0.01	.041	
298	230.0'	240.0'	10.0'	.018	0.70	<0.01	<0.02	.059	.014	0.55	<0.01	<0.01	.051	

SUPPLY
RECEIVED
 1965
 7/20/65 10:11:13:1:2:0:1:56

INDUSMIN LIMITED

SAMPLE RECORD

PROPERTY Fraser Bay Hill

SAMPLE NO.	FROM	TO	LENGTH	ASSAYS										DESCRIPTION
				-30 Crude					-30 +200 Product					
				Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	
299	240.0'	244.4'	4.4'	.024	1.25	<0.01	0.02	.060	.018	1.10	<0.01	<0.01	.049	
300	244.4'	245.5'	1.1'	.127	8.02	<0.01	0.13	.247	.130	7.80	<0.01	0.11	.235	
1100	245.5'	255.0'	9.5'	.014	0.63	<0.01	0.01	.045	.014	0.58	<0.01	<0.01	.037	
1101	255.0'	263.5'	8.5'	.014	0.62	<0.01	<0.01	.052	<.010	0.62	<0.01	<0.01	.044	
1102	263.5'	266.0'	2.5'	.167	12.90	<0.01	0.12	.419	.157	12.60	<0.01	0.98	.448	
1103	266.0'	275.0'	9.0'	.019	0.53	<0.01	<0.01	.045	.010	0.57	<0.01	<0.01	.040	
1104	275.0'	285.0'	10.0'	<.010	0.45	<0.01	<0.01	.041	<.010	0.34	<0.01	<0.01	.035	
1105	285.0'	295.0'	10.0'	<.010	0.42	<0.01	<0.01	.044	<.010	0.36	<0.01	<0.01	.038	
1106	295.0'	305.0'	10.0'	.013	0.42	<0.01	<0.01	.044	<.010	0.38	<0.01	<0.01	.040	
1107	305.0'	315.0'	10.0'	.014	0.59	<0.01	<0.01	.063	.011	0.51	<0.01	<0.01	.056	
1108	315.0'	326.3'	11.3'	.014	0.53	<0.01	<0.01	.043	.010	0.49	<0.01	<0.01	.039	
1109	326.3'	334.7'	8.3'	.056	3.34	<0.01	0.02	.114	.048	2.93	<0.01	<0.01	.104	
1110	334.7'	345.0'	10.3'	<.010	0.42	<0.01	<0.01	.032	<.010	0.31	<0.01	<0.01	.027	
1111	345.0'	355.0'	10.0'	<.010	0.20	<0.01	<0.01	.027	<.010	0.18	<0.01	<0.01	.025	

INDUSMIN LIMITED

PROPERTY Fraser Bay Hill

SAMPLE RECORD

SAMPLE NO.	FROM	TO	LENGTH	ASSAYS										DESCRIPTION
				-30 Crude					-30 +200 Product					
				Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	
1112	355.0'	365.0'	10.0'	.011	0.35	<0.01	<0.01	.043	<.010	0.29	<0.01	<0.01	.036	
1113	365.0'	375.0'	10.0'	.012	0.38	<0.01	<0.01	.047	<.010	0.35	<0.01	<0.01	.038	
1114	375.0'	385.0'	10.0'	.022	0.51	<0.01	<0.01	.043	.016	0.46	<0.01	<0.01	.038	
1115	385.0'	395.0'	10.0'	.017	0.41	<0.01	<0.01	.037	.019	0.39	<0.01	<0.01	.035	
1116	395.0'	405.0'	10.0'	<.010	0.24	<0.01	<0.01	.032	<.010	0.25	<0.01	<0.01	.029	
1117	405.0'	415.0'	10.0'	.016	0.35	<0.01	<0.01	.035	.012	0.30	<0.01	<0.01	.030	
1118	415.0'	425.0'	10.0'	.031	0.24	<0.01	<0.01	.029	.027	0.22	<0.01	<0.01	.027	
1119	425.0'	435.0'	10.0'	.016	0.24	<0.01	<0.01	.036	.014	0.21	<0.01	<0.01	.032	
1120	435.0'	450.0'	15.0'	.020	0.30	<0.01	<0.01	.041	.018	0.28	<0.01	<0.01	.034	
-	450.0'	460.0'	10.0'	-	-	-	-	-	-	-	-	-	-	Lamprophyre dyke
1121	460.0'	470.0'	10.0'	.044	0.20	<0.01	<0.01	.024	.039	0.19	<0.01	<0.01	.024	
1122	470.0'	480.0'	10.0'	.027	0.23	<0.01	<0.01	.029	.022	0.21	<0.01	<0.01	.026	
1123	480.0'	492.0'	12.0'	.024	0.25	<0.01	<0.01	.034	.019	0.22	<0.01	<0.01	.031	
-	492.0'	494.0'	2.0'	-	-	-	-	-	-	-	-	-	-	Lamprophyre dyke

SUBSIDIARY
MINING DIV.
RECEIVED
MAY 7 - 1985
P.M.
7:30, 10:11, 12:1, 2:3, 4:56

INDUSMIN LIMITED

PROPERTY Fraser Bay Hill

SAMPLE RECORD

SAMPLE NO.	FROM	TO	LENGTH	ASSAYS										DESCRIPTION
				-30 Crude					-30 +200 Product					
				Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	
1124	494.0'	505.0'	11.0'	.030	0.26	<0.01	<0.01	.036	.025	0.24	<0.01	<0.01	.032	
1125	505.0'	515.0'	10.0'	.013	0.25	<0.01	<0.01	.031	<.010	0.21	<0.01	<0.01	.029	
1126	515.0'	525.0'	10.0'	.017	0.36	<0.01	<0.01	.027	.013	0.32	<0.01	<0.01	.023	
1127	525.0'	535.0'	10.0'	.023	0.76	0.01	<0.01	.060	.014	0.72	0.01	<0.01	.050	
1128	535.0'	542.5'	7.5'	.053	1.56	0.01	0.02	.094	.043	1.49	0.01	0.01	.082	
-	542.5'	552.0'	9.5'	-	-	-	-	-	-	-	-	-	-	Sericite schist and quartzite
1129	552.0'	565.0'	13.0'	.055	1.27	<0.01	<0.01	.085	.048	1.08	<0.01	0.01	.074	
1130	565.0'	575.0'	10.0'	.035	0.43	<0.01	<0.01	.047	.027	0.36	<0.01	<0.01	.038	
1131	575.0'	585.0'	10.0'	.047	0.36	<0.01	<0.01	.034	.032	0.28	<0.01	<0.01	.025	
1132	585.0'	591.0'	6.0'	.046	0.23	<0.01	<0.01	.032	.044	0.19	<0.01	0.01	.027	

SUDBURY
 RECEIVED
 MAY 11 1985
 A.M. P.M.
 5:00 11:59 12:00 1:59

INDUSMIN LIMITED

PROPERTY Fraser Bay Hill

SAMPLE RECORD

SAMPLE NO.	FROM	TO	LENGTH	ASSAYS										DESCRIPTION
				-30 Crude					-30 +200 Product					
				Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	
1133	0.0'	10.0'	10.0'	.019	0.41	<0.01	<0.01	.041	.013	0.35	0.01	<0.01	.038	
1134	10.0'	20.0'	10.0'	.023	0.37	<0.01	<0.01	.045	.014	0.31	<0.01	<0.01	.042	
1135	20.0'	35.0'	15.0'	.019	0.48	<0.01	<0.01	.039	.011	0.27	<0.01	<0.01	.033	
1136	35.0'	45.0'	10.0'	.023	0.39	<0.01	<0.01	.046	.014	0.31	<0.01	<0.01	.036	
1137	45.0'	55.0'	10.0'	.024	0.47	<0.01	<0.01	.053	.017	0.38	<0.01	<0.01	.044	
1138	55.0'	65.0'	10.0'	.022	0.56	<0.01	<0.01	.049	.017	0.48	<0.01	<0.01	.042	
1139	65.0'	75.0'	10.0'	.028	0.50	<0.01	<0.01	.049	.021	0.47	<0.01	<0.01	.046	
1140	75.0'	85.0'	10.0'	.030	0.52	<0.01	<0.01	.056	.021	0.45	<0.01	<0.01	.049	
1141	85.0'	95.0'	10.0'	.024	0.34	<0.01	<0.01	.046	.013	0.26	<0.01	<0.01	.035	
1142	95.0'	105.0'	10.0'	.025	0.38	<0.01	<0.01	.041	.016	0.34	<0.01	<0.01	.035	
1143	105.0'	115.0'	10.0'	.023	0.35	<0.01	<0.01	.045	.018	0.27	<0.01	<0.01	.035	
1144	115.0'	130.0'	15.0'	.021	0.37	<0.01	<0.01	.051	.012	0.29	<0.01	<0.01	.038	
1145	130.0'	140.0'	10.0'	.019	0.35	<0.01	<0.01	.043	.011	0.29	<0.01	<0.01	.039	
1146	140.0'	150.0'	10.0'	.021	0.36	<0.01	<0.01	.041	.012	0.29	<0.01	<0.01	.032	

RECEIVED
 SUBSIDIARY
 11/2/66
 A.M.
 11/2/66

INDUSMIN LIMITED
SAMPLE RECORD

PROPERTY Fraser Bay Hill

SAMPLE NO.	FROM	TO	LENGTH	ASSAYS										DESCRIPTION
				-30 Crude					-30 +200 Product					
				Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	
1147	150.0'	160.0'	10.0'	.016	0.30	<0.01	<0.01	.042	.010	0.23	<0.01	<0.01	.031	
1148	160.0'	170.0'	10.0'	.088	0.37	<0.01	<0.01	.049	.078	0.30	<0.01	<0.01	.042	
1149	170.0'	180.0'	10.0'	.018	0.31	<0.01	<0.01	.044	.017	0.29	<0.01	<0.01	.039	
1150	180.0'	190.0'	10.0'	<.01	0.29	<0.01	<0.01	.042	<.010	0.25	<0.01	<0.01	.038	
1151	190.0'	200.0'	10.0'	<.01	0.30	<0.01	<0.01	.042	<.010	0.30	<0.01	<0.01	.037	
1152	200.0'	220.0'	20.0'	.021	0.92	<0.01	<0.01	.065	.020	0.81	<0.01	<0.01	.057	
1153	220.0'	230.0'	10.0'	.168	1.65	0.02	<0.01	.084	.165	1.51	<0.01	<0.01	.074	
1154	230.0'	240.0'	10.0'	.013	0.43	<0.01	<0.01	.050	.010	0.42	<0.01	<0.01	.044	
1155	240.0'	250.0'	10.0'	<.010	0.52	<0.01	<0.01	.053	<.010	0.47	<0.01	<0.01	.052	
1156	250.0'	260.0'	10.0'	.014	0.83	<0.01	<0.01	.081	.015	0.79	<0.01	<0.01	.081	
1157	260.0'	270.0'	10.0'	.024	1.34	<0.01	<0.01	.096	.019	1.26	<0.01	<0.01	.085	
1158	270.0'	280.0'	10.0'	<.010	0.47	<0.01	<0.01	.053	<.010	0.44	<0.01	<0.01	.044	
1159	280.0'	290.0'	10.0'	.041	0.79	<0.01	<0.01	.071	.015	0.71	<0.01	<0.01	.067	
1160	290.0'	300.0'	10.0'	.015	0.92	<0.01	<0.01	.093	.015	0.86	<0.01	<0.01	.083	

RECEIVED
MAY 7 - 1986

INDUSMIN LIMITED
SAMPLE RECORD

PROPERTY Fraser Bay Hill

SAMPLE NO.	FROM	TO	LENGTH	-30 Crude ASSAYS -30 +200 Product										DESCRIPTION
				Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	
1161	300.0'	310.0'	10.0'	.010	0.57	<0.01	<0.01	.070	<0.01	0.56	<0.01	<0.01	.063	
1162	310.0'	320.0'	10.0'	<.010	0.41	<0.01	<0.01	.053	<0.01	0.39	<0.01	<0.01	.045	
1163	320.0'	330.0'	10.0'	<.010	0.40	<0.01	<0.01	.048	<0.01	0.38	<0.01	<0.01	.039	
1164	330.0'	340.0'	10.0'	.010	0.48	<0.01	<0.01	0.52	<0.01	0.52	<0.01	<0.01	.048	
1165	340.0'	352.0'	12.0'	.044	2.92	<0.01	0.02	.150	.040	2.72	<0.01	<0.01	.137	
-	352.0'	353.9'	1.9'	-	-	-	-	-	-	-	-	-	-	Sericite schist & quartzite
1166	353.9'	360.0'	6.1'	.027	1.64	<0.01	<0.01	.107	.026	1.59	<0.01	<0.01	.094	
1167	360.0'	370.0'	10.0'	<.010	0.45	<0.01	<0.01	.048	<.010	0.38	<0.01	<0.01	.040	
1168	370.0'	380.0'	10.0'	.011	0.39	<0.01	<0.01	.042	<.010	0.36	<0.01	<0.01	.040	
1169	380.0'	390.0'	10.0'	.010	0.34	<0.01	<0.01	.044	<.010	0.30	<0.01	<0.01	.038	
1170	390.0'	400.0'	10.0'	.014	0.45	<0.01	<0.01	.040	.010	0.41	<0.01	<0.01	.035	
1171	400.0'	410.0'	10.0'	.011	0.34	<0.01	<0.01	.040	<.010	0.32	<0.01	<0.01	.034	
1172	410.0'	420.0'	10.0'	.013	0.31	<0.01	<0.01	.037	.011	0.27	<0.01	<0.01	.031	
1173	420.0'	430.0'	10.0'	.011	0.37	<0.01	<0.01	.045	<.010	0.36	<0.01	<0.01	.038	

SUBSIDIARY
 RECEIVED
 1974-11-29
 A.M. P.M.
 7:00 AM - 11:00 AM

INDUSMIN LIMITED

PROPERTY Fraser Bay Hill

SAMPLE RECORD

SAMPLE NO.	FROM	TO	LENGTH	ASSAYS										DESCRIPTION
				-30 Crude					-30 +200 Product					
				Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	
1174	430.0'	440.0'	10.0'	.068	2.80	<0.01	0.03	.135	.063	2.52	<0.01	0.02	.122	
1175	440.0'	450.0'	10.0'	.025	0.78	<0.01	<0.01	.069	.022	0.71	<0.01	<0.01	.060	
1176	450.0'	460.0'	10.0'	.032	0.37	<0.01	<0.01	.044	.025	0.32	<0.01	<0.01	.036	
1177	460.0'	470.0'	10.0'	.055	1.42	<0.01	0.02	.086	.037	1.17	<0.01	<0.01	.066	
1178	470.0'	479.0'	9.0'	.052	0.87	<0.01	0.01	.062	.043	0.72	<0.01	<0.01	.054	
-	479.0'	491.0'	12.0'	-	-	-	-	-	-	-	-	-	-	Sand - washed away
1179	491.0'	500.0'	9.0'	.041	1.10	<0.01	<0.01	.080	.037	0.97	<0.01	<0.01	.069	
1180	500.0'	510.0'	10.0'	.033	0.59	<0.01	<0.01	.060	.023	0.52	<0.01	<0.01	.053	
1181	510.0'	520.0'	10.0'	.036	0.43	<0.01	<0.01	.050	.021	0.37	<0.01	<0.01	.044	
1182	520.0'	530.0'	10.0'	.091	2.27	<0.01	<0.01	.115	.070	1.96	<0.01	<0.01	.094	
1183	530.0'	538.0'	8.0'	.032	0.58	0.01	<0.01	.058	.022	0.45	<0.01	<0.01	.049	
-	538.0'	539.2'	1.2'	-	-	-	-	-	-	-	-	-	-	Sericite schist
1184	539.2'	544.3'	5.1'	.155	1.57	<0.01	<0.01	.082	.121	1.33	<0.01	<0.01	.072	
-	544.3'	546.7'	2.4'	-	-	-	-	-	-	-	-	-	-	Sericite schist

SUPPLY
RECEIVED
 MAY 7 - 1985
 7:8:9:10:11:12:1:2:3:4:5:6


INDUSMIN LIMITED

PROPERTY Fraser Bay Hill

SAMPLE RECORD

SAMPLE NO.	FROM	TO	LENGTH	ASSAYS										DESCRIPTION
				-30 Crude					-30 +200 Product					
				Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	Fe ₂ O ₃	Al ₂ O ₃	CaO	MgO	TiO ₂	
1185	546.7'	551.4'	4.7'	.298	0.95	<0.01	<0.01	.054	.207	0.81	<0.01	<0.01	.047	
-	551.4'	556.5'	5.1'	-	-	-	-	-	-	-	-	-	-	Sericite schist
1186	556.5'	565.0'	8.5'	.132	1.68	<0.01	<0.01	.113	.112	1.47	<0.01	0.02	.099	
1187	565.0'	575.0'	10.0'	.058	0.95	<0.01	<0.01	.071	.050	0.86	<0.01	<0.01	.068	
1188	575.0'	585.4'	10.4'	.048	0.56	<0.01	<0.01	.052	.032	0.48	<0.01	<0.01	.042	
-	585.4'	586.8'	1.4'	-	-	-	-	-	-	-	-	-	-	Sericite schist
1189	586.8'	595.0'	8.2'	.060	0.57	<0.01	<0.01	.052	.037	0.53	<0.01	<0.01	.043	
1190	595.0'	605.0'	10.0'	.035	0.55	<0.01	<0.01	.048	.030	0.43	<0.01	<0.01	.042	
1191	605.0'	615.0'	10.0'	.036	0.48	<0.01	<0.01	.048	.028	0.41	<0.01	<0.01	.042	
1192	615.0'	625.0'	10.0'	.034	0.35	<0.01	<0.01	.044	.022	0.31	<0.01	<0.01	.036	
1193	625.0'	635.0'	10.0'	.043	0.49	<0.01	<0.01	.050	.031	0.43	<0.01	<0.01	.043	
1194	635.0'	645.0'	10.0'	.044	0.45	<0.01	<0.01	.046	.029	0.39	<0.01	<0.01	.035	
1195	645.0'	652.0'	7.0'	.092	1.36	<0.01	<0.01	.070	.073	1.14	<0.01	0.02	.057	

SUBSIDIARY
 MINING DIV.
RECEIVED
 1967-7-12
 A.M. 7:8 9:10 11 12 P.M. 1:2 3:30 4:40



KILLARNEY TP

M-969

1 5/16 INCH = 1 MILE
1 MILE

Order No. W.34/85 N.E.R.

Surface & Mining Rights

Frazier

Boy

Lake Huron

Order No. W.34/85 N.E.R.

Surface & Mining Rights

Boddeley Island



41104SE002 0015 KILLARNEY

900

Ministry of
Natural Resources

Ontario

86-34

Report of Work
(Geophysical, Geological,
Geochemical and Expenditures)

(Killarney Twp.)

M. 969

2.9.120
Mining Act 2.9.120

File: S.626348

- Instructions: - Please type or print.
- If number of mining claims traversed exceeds space on this form, attach a list.
- Note: - Only days credits calculated in the "Expenditures" section may be entered in the "Expend. Days Cr." columns.
- Do not use shaded areas below.

Type of Survey(s) ANALYSIS OF DRILL CORE		Township or Area KILLARNEY
Claim Holder(s) FALCONBRIDGE LIMITED		Prospector's Licence No. A21647
Address P.O. BOX 40, COMMERCE COURT WEST, TORONTO, ONTARIO, M5L 1B4		
Survey Company	Date of Survey (from & to) Day Mo. Yr. Day Mo. Yr.	Total Miles of line Cut
Name and Address of Author (of Geo-Technical report)		

Credits Requested per Each Claim in Columns at right

Special Provisions	Geophysical	Days per Claim
For first survey: Enter 40 days. (This includes line cutting)	Electromagnetic	
	Magnetometer	
	Radiometric	
	Other	
	Geological	
For each additional survey: using the same grid: Enter 20 days (for each)	Geological	
	Geochemical	
Man Days Complete reverse side and enter total(s) here	Geophysical	Days per Claim
	Electromagnetic	
	Magnetometer	
	Radiometric	
	Other	
Airborne Credits Note: Special provisions credits do not apply to Airborne Surveys.	Geological	
	Geochemical	
Airborne Credits	Electromagnetic	Days per Claim
	Magnetometer	
	Radiometric	

Mining Claims Traversed (List in numerical sequence)

Prefix	Mining Claim		Expend. Days Cr.	Prefix	Mining Claim		Expend. Days Cr.
	Number	Number			Number	Number	
S	626348		60				
	626351		60				
	626352		60				
	626353		60				
	626354		48				
	626355		48				
	626356		48				
	626357		48				
	626358		60				
	626359		60				
	626360		4				
	626361		60				
	626362		60				
	629882		60				
	629883		60				
	648304		50				

Expenditures (excludes power stripping)

Type of Work Performed Analysis as per Sect 77(19)
Performed on Claim(s) 626359, 626361 and 626362
Calculation of Expenditure Days Credits
Total Expenditures \$ 12690 + 15 = Total Days Credits 846
Instructions Total Days Credits may be apportioned at the claim holder's choice. Enter number of days credits per claim selected in columns at right.

Total number of mining claims covered by this report of work.

16

Date May 9, 1986	Recorded Holder or Agent (Signature) <i>J. B. Cella</i>
----------------------------	--

For Office Use Only	
Total Days Cr. Recorded 846	Date Recorded 1986 05 13
Date Approved as Recorded <i>W.S.V.</i>	Ministry Director <i>C. Miller</i>

Certification Verifying Report of Work

I hereby certify that I have a personal and intimate knowledge of the facts set forth in the Report of Work annexed hereto, having performed the work or witnessed same during and/or after its completion and the annexed report is true.		
Name and Postal Address of Person Certifying Tony Masciotra, Falconbridge Limited P.O. Box 40, Commerce Court West, Toronto, Ontario M5L 1B4		
Date Certified May 9, 1986	Certifying Signature <i>Tony Masciotra</i>	




Costs involved in the chemical analysis of Indusmin Diamond Drill Core for individual sample:

1. Sample preparation, geologist + core splitting = \$ 7.50
2. Laboratory cost: \$25.00/hr. x 1.5 hrs. = 37.50

Grand Total Cost per sample = \$45.00

Assay information on six diamond drill holes drilled on claims 626359, 626361 and 626362 submitted for assessment work:

Hole #	No. of Samples	Days Work
A-1	52	52 x \$45 a sample = <u>\$2,340</u> = 156 \$15/day
B-1	50	50 x \$45 a sample = <u>\$2,250</u> = 150 \$15/day
B-2	27	27 x \$45 a sample = <u>\$1,215</u> = 81 \$15/day
B-3	28	28 x \$45 a sample = <u>\$1,260</u> = 84 \$15/day
B-4	62	62 x \$45 a sample = <u>\$2,790</u> = 186 \$15/day
C-1	63	63 x \$45 a sample = <u>\$2,835</u> = 189 \$15/day
		TOTAL DAYS WORK = 846 ***



[Signature]
 Chief Accountant

[Signature]
 Project Engineer