



41P14NE0111 22 HALLIDAY

010

Diamond Drilling

Township of HALLIDAY

Report NO: 22

Work performed by: Rio Tinto Canadian Exploration Ltd.

Claim NO	Hole NO	Footage	Date	Note
L 298948	A-2 (1)	453'	Dec/75	(1)

Notes:

(1) #80/76

RIO TINTO CANADIAN EXPLORATION LIMITED
DIAMOND DRILL RECORD

HOLE No:

A-2


PAGE No:

2

FOOTAGE		DESCRIPTION	SAMPLE No	FOOTAGE		LENGTH	% Cu	% Zn	oz/t Au	oz/t Ag
from	to			from	to					
		25% black matrix, graphitic								
162.0	267.0	RHYOLITE BRECCIA								
		0.2-10 cm light grey angular to sub- angular rhyolite fragments in a fine grained black hard matrix.								
		10-15% matrix								
		1-2 % pyrite disseminated and 0.5-1cm fine grained pyrite fragments.								
		Pyrite fragments sometimes have a 1-2 mm granular secondary pyrite rim.								
		250.0-267.0								
		Darker with 15-20% pyrite								
		250.0-255.0	203134	250.0	255.0	5.0	0.01	0.03	tr	nil
		30-35% pyrite as granular fragments and 1-2 mm secondary pyrite rim's on rhyolite fragments, 10% black mat- rix, graphitic								
267.0	End	RHYOLITE AGGLOMERATE								
		0.1-15 cm light grey siliceous angular rhyolite fragments in a 10-15% fine grained black, siliceous matrix.								
		Larger fragments are well fractured. Occassional tuffaceous rhyolite frag- ments consisting 1-4 cm massive light grey to white subrounded rhyolite frag- ments.								
		5-10% pyrite, disseminated in rhyolite fragments and matrix and occasionally as 0.1-2 cm blebs or fragments.								

PAGE No :
3

R.A.M.L. 259



HALLIDAY TWP, ONTARIO

NTS.
41-P-14.

ALLERSTON OPTION
D.D.H. A-2



1" = 400'

WB/25/3/

76/80 HALLIDAY & SOTHMAN TWP.S.

S O T H M A N T W P.

HALLIDAY TWP.



N. T. S.
41 - P - 14

RIO TINTO CANADIAN EXPLORATION LTD.

ALLERSTON OPTION - ONT.

LOCATION MAP

Sept. - 1975

W. B. / e. b.

DWG L - 2716



41P14NE0111 22 HALLIDAY