

DIA



52F16SW8290 18 LAVAL

010


TOWNSHIP: LavalREPORT NO: 18WORK PERFORMED FOR: Champion Bear ResourcesRECORDED HOLDER: SAME AS ABOVE : OTHER

<u>CLAIM NO.</u>	<u>HOLE NO.</u>	<u>FOOTAGE</u>	<u>DATE</u>	<u>NOTE</u>
K161411	BT01	406	Feb 92	(1)
K161411	BT02	486	Feb 92	"
K1144900	BT03	486	Feb 92	"
K1144900	BT04	426	Mar 92	"
K1144900	BT05	327	Mar 92	"
K1144900	BT06	355	Mar 92	"
K1161173	BT07	396	Mar 92	"
K1144900	BT08	166	Mar 92	"
K1144900	BT09	126	Mar 92	"
K1144900	BT10	125	Mar 92	"
K1133507	BT11	406	Mar 92	"

NOTES:

Report of Work 9310 00035

Filed on May 3rd 1993



52F16SW8290 18 LAVAL

020

CHAMPION BEAR RESOURCES LTD.

BEARTRACK LAKE PROJECT

DIAMOND DRILL LOGS


1991 - 1992

SUMMARY OF DRILL DATA ON BORSURV FILES AT BearTrack Lake

Hole No.	Grid Name	METERS		Elevation	Units	Grid		Depth	Wedges	Litho Units	No. of Assays	Averaged Zones		Elements
		Eastings	Northings			Dip	Bearing					Total	Named	
BT01	BearTrack	-1100.00	40.00	0.00	feet	-45.00	180.00	406.00	0	0	5	0	0	10(Sample, Au(ppb), Cu(ppm), Pb(ppm), Zn(ppm), Ag(ppm), Ni(ppm), Mn(ppm), Fe(%) , As(ppm))
BT02	BearTrack	-1100.00	215.00	0.00	feet	-45.00	180.00	486.00	0	0	29	0	0	10(Sample, Au(ppb), Cu(ppm), Pb(ppm), Zn(ppm), Ag(ppm), Ni(ppm), Mn(ppm), Fe(%) , As(ppm))
BT03	BearTrack	-800.00	125.00	0.00	feet	-45.00	180.00	486.00	0	0	21	0	0	10(Sample, Au(ppb), Cu(ppm), Pb(ppm), Zn(ppm), Ag(ppm), Ni(ppm), Mn(ppm), Fe(%) , As(ppm))
BT04	BearTrack	-800.00	80.00	0.00	feet	-45.00	231.00	426.00	0	0	21	0	0	10(Sample, Au(ppb), Cu(ppm), Pb(ppm), Zn(ppm), Ag(ppm), Ni(ppm), Mn(ppm), Fe(%) , As(ppm))
BT05	BearTrack	-575.00	75.00	0.00	feet	-45.00	231.00	327.00	0	0	5	0	0	10(Sample, Au(ppb), Cu(ppm), Pb(ppm), Zn(ppm), Ag(ppm), Ni(ppm), Mn(ppm), Fe(%) , As(ppm))
BT06	BearTrack	-475.00	135.00	0.00	feet	-45.00	231.00	355.00	0	0	11	0	0	10(Sample, Au(ppb), Cu(ppm), Pb(ppm), Zn(ppm), Ag(ppm), Ni(ppm), Mn(ppm), Fe(%) , As(ppm))
BT07	BearTrack	-200.00	125.00	0.00	feet	-45.00	231.00	396.00	0	0	9	0	0	10(Sample, Au(ppb), Cu(ppm), Pb(ppm), Zn(ppm), Ag(ppm), Ni(ppm), Mn(ppm), Fe(%) , As(ppm))
BT08	BearTrack	-839.00	58.00	0.00	feet	-45.00	201.00	166.00	0	0	3	0	0	10(Sample, Au(ppb), Cu(ppm), Pb(ppm), Zn(ppm), Ag(ppm), Ni(ppm), Mn(ppm), Fe(%) , As(ppm))
BT09	BearTrack	-739.00	60.00	0.00	feet	-55.00	201.00	126.00	0	0	7	0	0	10(Sample, Au(ppb), Cu(ppm), Pb(ppm), Zn(ppm), Ag(ppm), Ni(ppm), Mn(ppm), Fe(%) , As(ppm))
BT10	BearTrack	-850.00	55.00	0.00	feet	-45.00	201.00	125.00	0	0	1	0	0	10(Sample, Au(ppb), Cu(ppm), Pb(ppm), Zn(ppm), Ag(ppm), Ni(ppm), Mn(ppm), Fe(%) , As(ppm))
BT11	BearTrack	-1200.00	-625.00	0.00	feet	-45.00	180.00	406.00	0	0	22	0	0	10(Sample, Au(ppb), Cu(ppm), Pb(ppm), Zn(ppm), Ag(ppm), Ni(ppm), Mn(ppm), Fe(%) , As(ppm))

Total Holes: 11 Total depth: 3705.00 Total assays: 136


BEARTRACK LAKE



R 1144900

R 1133500

Scale 1:5000



CHAMPION BEAR RESOURCES LTD.

DIAMOND DRILL LOG

PROPERTY: BearTrack Lake
 HOLE No.: BT01
 Collar Eastings: -1100.00
 Collar Northings: 40.00
 Collar Elevation: 0.00
 Grid: BearTrack

Collar Inclination: -45.00
 Grid Bearing: 0.00
 Final Depth: 406.00 feet

Logged by: H. Petak
 Date: Feb. 19-22, 1992
 Down-hole Survey:

FROM	TO	LITHOLOGICAL DESCRIPTION	FROM	TO	WIDTH	ASSAYS												
						Sample	Au(ppb)	Cu(ppa)	Pb(ppa)	Zn(ppa)	Ag(ppa)	Ni(ppa)	Mn(ppa)	Fe(%)	As(ppa)			
0	11	(CASING)																
11	406	(ANDESITE)	0.00	45.80	45.80	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	
		Dark green to dark greyish green colour; mostly vfg chl, variable amounts of fldsp, very little qtz; Foliation is moderately to well developed with angles of 25 to 30 deg to ca. Carb veinl occur quite frequ throuth the sect.	45.80	49.60	3.80	4101	15	24	17	68	0.1	71	776	5.00	37			
		28.4 - 50.5 incr amt carb veinl, mostly parll to sub-parll to fol, minor crosscut;	49.60	100.50	50.90	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.			
		100.50 - 101.50 1.00 4102 29 86 9 46 TRACE 108 411 4.32 19	100.50	101.50	1.00	4102	29	86	9	46	TRACE	108	411	4.32	19			
		101.50 - 406.00 304.50 N.S. N.S. N.S. N.S. N.S. N.S. N.S. N.S. N.S. N.S.	101.50	406.00	304.50	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.			
		45.8 - 49.6 Finl dissea py, mostly parll fol;																
		78 - 102 SHEAR ZONE with sporadic dissea of fg py (< 5% incl 0.25" band of semi-mass py in one shear;																
		121.5 - 126 strong shearing and fragmentation, no min;																
		139 & 140 shears, no min;																
		156 3" qtz vein, white, no min;																
		167 1.5" qtz vein, white, no min;																
		167.8 - 170 dissea py (< 5%) mostly along fol;																
		183.5 0.25" qtz vein, white, no min;																
		195 - 196 shear, no min;																
		257 1" dissea py (< 5%);																
		306 shear, no min;																
		336 - 350.6 Fracture zone, no min;																
406.		(END OF HOLE)																

HOLE No: BT01

CHAMPION BEAR RESOURCES LTD.

DIAMOND DRILL LOG

PROPERTY: BearTrack Lake
 HOLE No.: BTO2
 Collar Eastings: -1100.00
 Collar Northings: 215.00
 Collar Elevation: 0.00
 Grid: BearTrack

Collar Inclination: -45.00
 Grid Bearing: 180.00
 Final Depth: 486.00 feet

Logged by: H. Petak
 Date: Feb. 22-27, 1992
 Down-hole Survey:

FROM	TO	LITHOLOGICAL DESCRIPTION	FROM	TO	WIDTH	Sample	ASSAYS										
							Au(ppb)	Cu(ppa)	Pb(ppa)	Zn(ppa)	Ag(ppa)	Ni(ppa)	Mn(ppa)	Fe(%)	As(ppa)		
0	107	(CASING)															
107	296.2	(ANDESITE)	0.00	127.00	127.00	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		Dark green to greyish green colour; generally vfg with mod to well devel foliation at 30 to 45 deg to ca; mainly chl (after hbl ?), minor fldsp, little qtz; in places some lge turu;	127.00	130.50	3.50	4103	11	9	14	63	TRACE	74	512	3.23	13		
			130.50	138.70	8.20	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
			138.70	148.60	9.90	4104	41	19	14	152	0.6	78	867	3.16	20		
			148.60	164.30	15.70	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		SULFIDE MINERALIZATION is quite wide-spread throughout the section consisting mostly of fine disse py and minor po, incl occl narrow (up to few inch wide) stringers to semi-mass bands. The stringers often occur with turu. Also fairly common are vfg disse of agt.	164.30	164.70	0.40	4105	177	75	14	62	2.1	153	759	5.86	125		
			164.70	165.50	0.80	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
			165.50	168.30	2.80	4106	7	19	8	69	TRACE	65	708	3.50	20		
			168.30	175.80	7.50	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		ALTERATION zones of 1 to 2 ft in length, consisting of feld spathization and carbonatization, can be noted occas. Carb frequ occurs as fracture fillings.	175.80	177.10	1.30	4107	21	117	21	137	0.5	76	620	7.41	32		
			177.10	205.00	27.90	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
			205.00	206.50	1.50	4108	11	57	10	216	TRACE	73	805	6.17	114		
			206.50	228.30	21.80	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
			228.30	234.30	6.00	4109	13	30	14	37	TRACE	63	321	2.29	16		
			234.30	244.50	10.20	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		127 - 130.5 < 3% disse py, incl 5 - 10% from 127 - 127.5;	244.50	248.70	4.20	4110	TRACE	49	12	170	0.7	57	753	6.98	18		
		138.7 - 148.6 < 3% fine disse py;															
		151 - 153.6 strong SHEAR ZONE; no min;															
		164.3 - 164.7 5 - 10% py assoc w turu and agt;															
		165.5 - 168.3 fine disse py															
		175.8 - 177.1 < 5% disse py incl heavy stringer at 176.7;															
		205 - 206.5 < 5% disse py;															
		228.3 - 234.3 < 3% disse py, incl heavy stringer at 231.4;															
		a 1" qtz vein at 233.5 contains some py (< 5%);															
		234.6 - 235.2 qtz vein, no min;															
		241 5" qtz vein, no min;															
		244.5 - 248.7 < 3% disse py, incl 0.25" of 50% py at 245;															
296.2	486	(DIORITE)	248.70	303.00	54.30	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		Medium grey colour; m- to lg; massive to poorly fol; in places the texture suggests micro-brecc.	303.00	304.00	1.00	4111	69	57	10	216	TRACE	73	805	6.17	114		
			304.00	334.30	30.30	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
			334.30	337.00	2.70	4112	TRACE	37	11	23	TRACE	50	573	1.68	8		
		303 - 304 < 1% disse py, incl 0.5" of 30% py;	337.00	370.40	33.40	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		334.3 - 337 5 - 10% py in SHEAR ZONE;	370.40	372.80	2.40	4113	TRACE	30	14	37	TRACE	63	321	2.29	16		
		370.4 - 372.8 disse py on both sides of a 1" qtz filled shear	372.80	377.30	4.50	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		377.2 - 381 heavy FRACTURE ZONE with brecc containing fine disse py (< 10%);	377.30	381.00	3.70	4114	TRACE	17	16	91	TRACE	85	936	3.51	3		
				381.00	392.50	11.50	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		392.5 - 400.5 strong DEFORMATION ZONE (fold & brecc) with up to 40% py;	392.50	400.50	8.00	4115	213	30	14	37	TRACE	63	321	2.29	16		
				400.50	454.00	53.50	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.

HOLE No: BTO2

CHAMPION BEAR RESOURCES LTD.

DIAMOND DRILL LOG

PROPERTY: BearTrack Lake
HOLE No.: BT02

Page 2

FROM	TO	LITHOLOGICAL DESCRIPTION	FROM	TO	WIDTH	Sample	ASSAYS									
							Au(ppb)	Cu(ppm)	Pb(ppm)	Zn(ppm)	Ag(ppm)	Ni(ppm)	Mn(ppm)	Fe(%)	As(ppm)	
454	458	c 3% fine disse py, incl a massive and semi-massive band at 454.5 and 457 resp;	454.00	458.00	4.00	4116	203	95	11	188	0.1	33	416	5.09	54	
			458.00	486.00	28.00	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
4 86.		(END OF HOLE)														

HOLE No: BT02

CHAMPION BEAR RESOURCES LTD.

DIAMOND DRILL LOG

PROPERTY: BearTrack Lake
 HOLE No.: BT03
 Collar Eastings: -800.00
 Collar Northings: 125.00
 Collar Elevation: 0.00
 Grid: BearTrack

Collar Inclination: -45.00
 Grid Bearing: 180.00
 Final Depth: 486.00 feet

Logged by: H. Petak
 Date:
 Down-hole Survey:

FROM	TO	LITHOLOGICAL DESCRIPTION	FROM	TO	WIDTH	ASSAYS												
						Sample	Au(ppb)	Cu(ppa)	Pb(ppa)	Zn(ppa)	Ag(ppa)	Ni(ppa)	Mo(ppa)	Fe(%)	As(ppa)			
0	36	(CASING)																
36	41	(ANDESITE) Grey to dark greenish gray, (g, fol, occas tuffac; containing occas dissea py;	0.00	38.60	38.60	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	
41	357	(DIORITE) Very dark greenish grey to grayish, a- to cg, weak to mod fol at 40 to 45 deg to ca; hbl, chl (after hbl ?), fldsp, little qtz; in places evidence of consid brecc; 38.6 - 41.4 < 3% dissea py incl band of 20% at 39.3; 47.5 - 48.5 weak to heavy dissea py in chloritic sect; mod magnetic due to fine dissea agt; 97.7 - 99 mafic dyke w < 1% dissea py; 106.0 - 109.7 andesitic section, vfg, w felsic veinlts and little fine dissea py; 111.7 - 112 carbonate; 115.6 - 121.5 mafic dyke, avg < 3% py; incl felsic sect at 116 - 116.6 consist of pegs and carb material and a 1" pegs in the core part of dyke; py incrs to 5 - 10% in vicity of both contacts to pegs core; 121.5 - 138 mylonitic texture; 138 - 148 SHEAR ZONE with local graph and bands of semi- massive to massive py from 141 - 144; carbonate veining; 169 - 171 mafic dyke, trc of dissea py; 186.1 - 186.6 qtz vein w turas; 225.8 - 226.6 mafic dyke with 5 - 10% py in the lower part; 240 - 241 felsic dyke, fldsp; 245.4 - 246 mafic dyke; 246.8 - 249.2 mafic dyke; 276.6 - 276.8 qtz vein with turas; 276.8 - 277.5 < 1% fine dissea py; 281 - 282 mafic dyke with carb veinlts in center, trc of fine py in mafic part; 355 1.5" qtz vein, no sin;	38.60	41.40	2.80	4118	29	63	11	165	0.1	80	795	5.44	28			
			41.40	47.50	6.10	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	
			47.50	48.50	1.00	4117	46	314	10	405	0.3	112	633	6.13	75			
			48.50	115.60	67.10	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	
			115.60	121.50	5.90	4119	TRACE	21	16	128	TRACE	33	641	4.83	18			
			121.50	141.00	19.50	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	
			141.00	144.00	3.00	4120	124	347	18	122	0.4	85	1520	8.86	160			
				144.00	225.80	81.80	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	
			225.80	226.60	0.80	4121	18	280	6	312	0.1	101	789	7.16	15			
357	486	(MAFIC VOLCANIGENIC ROCK) ANDES TO DAC COMP	226.60	378.30	151.70	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	

HOLE No: BT03

CHAMPION BEAR RESOURCES LTD.

DIAMOND DRILL LOG

PROPERTY: BearTrack Lake
HOLE No.: BT03

Page 2

FROM	TO	LITHOLOGICAL DESCRIPTION	FROM	TO	WIDTH	Sample	ASSAYS									
							Au(ppb)	Cu(ppa)	Pb(ppa)	Zn(ppa)	Ag(ppa)	Ni(ppa)	Mn(ppa)	Fe(I)	As(ppa)	
		Dark greenish-grey, weak to mod fol; vfg disse py (< 31)	378.30	385.50	7.20	4122	391	198	17	662	0.4	127	830	6.77	84	
		thruout most of the section; portions of the sect are	385.50	396.00	10.50	4123	7	104	8	134	TRACE	88	811	4.38	17	
		weak to mod magnetic due to some disse agt;	396.00	406.00	10.00	4124	7	128	9	109	0.4	95	800	5.02	22	
			406.00	416.00	10.00	4125	5	111	8	109	0.5	99	811	5.21	14	
360		4" qtz vein with turn;	416.00	422.00	6.00	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	
363.5		shear with 4" of 5 - 10% py at upper contact;	422.00	426.00	4.00	4126	5	67	10	121	0.2	86	831	4.49	15	
378.3 - 385.5		heavy disse and bands of semi-massive py;	426.00	431.00	5.00	4127	14	74	8	166	0.4	94	882	5.00	23	
		incl 2" qtz vein at 378.7;		431.00	453.00	22.00	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	
385.5 - 396		3 - 5% fine disse py;	453.00	456.00	3.00	4128	TRACE	68	15	95	TRACE	68	625	5.09	13	
396 - 406		fine disse py;	456.00	486.00	30.00	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	
406 - 416		fine disse py;														
422 - 426		fine disse py;														
426 - 431		fine disse py;														
453 - 456		5 - 10% disse py;														

486. (END OF HOLE)

HOLE No: BT03

CHAMPION BEAR RESOURCES LTD.

DIAMOND DRILL LOG

PROPERTY: BearTrack Lake
HOLE No.: BT04
Collar Eastings: -800.00
Collar Northings: 80.00
Collar Elevations: 0.00

Collar Inclination: -45.00
Grid Bearing: 231.00
Final Depth: 426.00 feet

Logged by: H. Petak
Date:
Down-hole Survey:

FROM	TO	LITHOLOGICAL DESCRIPTION	FROM	TO	WIDTH	Sample	ASSAYS										
							Au(ppb)	Cu(ppm)	Pb(ppm)	Zn(ppm)	Ag(ppm)	Ni(ppm)	Mn(ppm)	Fe(%)	As(ppm)		
0	5	(CASING)															
5	295	(DIORITE)	0.00	21.50	21.50	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		Dark grey to greenish-grey, fg to cg, in general weakly foliated with massive sections which are usually either very fine- or coarse-grained; mostly hbl and fldsp, some chl (after hbl ?), very little or no qtz; finely disseminated (< 1%) throughout the section; frequ carb veining;	21.50	25.00	3.50	4129	TRACE	54	7	110	TRACE	74	585	3.00	3		
			25.00	31.30	6.30	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
			31.30	32.20	0.90	4130	TRACE	43	TRACE	99	TRACE	111	746	3.75	TRACE		
			32.20	85.00	52.80	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
			85.00	86.00	1.00	4131	23	108	4	245	0.2	95	970	7.97	20		
			86.00	104.00	18.00	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		21.5 - 25 SHEAR ZONE with up to 3% py;	104.00	104.80	0.80	4132	144	1116	4	813	0.7	136	970	7.97	20		
		31.3 - 32.2 SHEAR ZONE with up to 3% py and carb filling;	104.80	162.00	57.20	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		40 - 42.4 strong SHEAR sub-parallel to core axis; carb filling, < 1% py;	162.00	168.00	6.00	4133	287	177	476	1688	3.3	168	623	7.74	170		
				168.00	253.80	85.80	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		85 - 86 5 - 10% py; 0.25% qtz vein at 85;	253.80	255.00	1.20	4134	12	77	9	135	0.2	137	798	4.73	10		
		95 1" qtz vein;		255.00	264.00	9.00	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		97 - 98 2 qtz veins (2" and 1") with tur; 1" qtz vein;	264.00	265.60	1.60	4135	5	38	TRACE	76	TRACE	106	840	3.72	TRACE		
		100 1" qtz vein;		265.60	289.60	24.00	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		104 - 104.6 3 - 5% disseminated py;	289.60	291.00	1.40	4136	7	178	8	80	0.6	96	707	5.08	13		
		162 - 168 SULFIDE ZONE with heavy disseminated py incl a 1" band of semi-massive py at 163.5 and a massive band at 165.4 - 166;															
		168 - 168.7 qtz vein with tur;															
		183.8 - 185.5 mafic dyke;															
		192.7 - 195 fracture zone filled with qtz and carbonate;															
		216 shear, no min;															
		244 - 245 fracture zone, fractures filled with carbonate; some specks of py;															
		254.5 1" qtz vein with tur, some disseminated py below lower contact (< 3% py);															
		258 2" carbonate;															
		264 - 265 qtz filled shear with some specks of py;															
		266 1" carbonate;															
		276.3 - 276.7 felsic dyke, apple green;															
		289.8 - 290.4 felsic dyke, same as above, some fine disseminated py below lower contact;															
295	426	(ANDESITE)	291.00	379.00	88.00	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		Dark green, fine grained, weakly to mod foliated, texture indicative of strong micro-breccia;	379.00	381.00	2.00	4137	TRACE	81	6	88	0.4	101	793	4.77	9		
			381.00	384.00	3.00	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
			384.00	386.00	2.00	4138	5	135	2	128	0.3	107	762	5.34	13		
		295 - 296.3 FRACTURE ZONE, blocky;	386.00	426.00	40.00	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.

HOLE No: BT04

CHAMPION BEAR RESOURCES LTD.

DIAMOND DRILL LOG

PROPERTY: BearTrack Lake
HOLE No.: BT04

Page 2

FROM	TO	LITHOLOGICAL DESCRIPTION	FROM	TO	WIDTH	ASSAYS													
						Sample	Au(ppb)	Cu(ppm)	Pb(ppm)	Zn(ppm)	Ag(ppm)	Ni(ppm)	Mn(ppm)	Fe(%)	As(ppm)				
317.5	319	injection of some felsic dyke material, same as above;																	
324		qtz, carb, turq;																	
325.7		2" qtz, carb, turq;																	
326	330	1 - 3% fine disse py;																	
335.4		1.5" qtz and carb;																	
337.3	337.8	qtz, carb, turq;																	
367	370	FRACTURE ZONE, blocky;																	
376		FRACTURE, blocky;																	
379	381	fine disse py above and below a 2" qtz vein at 380;																	
384	386	fine disse py;																	
397	403	very blocky, some core lost;																	
420		fracture, filled with carb and some very fine py																	
4 26.		(END OF HOLE)																	

HOLE No: BT04

CHAMPION BEAR RESOURCES LTD.

DIAMOND DRILL LOG

PROPERTY: BearTrack Lake
 HOLE No.: BT05
 Collar Eastings: -575.00
 Collar Northings: 75.00
 Collar Elevation: 0.00
 Grid: BearTrack

Collar Inclination: -45.00
 Grid Bearing: 231.00
 Final Depth: 327.00 feet

Logged by: H. Petak
 Date:
 Down-hole Survey:

FROM	TO	LITHOLOGICAL DESCRIPTION	FROM	TO	WIDTH	Sample	ASSAYS								
							Au(ppb)	Cu(ppm)	Pb(ppm)	Zn(ppm)	Ag(ppm)	Ni(ppm)	Mn(ppm)	Fe(%)	As(ppm)
0	10	(CASING)													
10	327	(DIORITE)	0.00	43.20	43.20	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	
		Dark greenish grey, generally medium to coarse grained, consisting of hbl, fldsp, some chl (after hbl ?), little or no qtz, poorly to mod foliated (30 to 45 deg to cal), in places massive;	43.20	44.70	1.50	4139	12	250	15	157	0.5	88	583	7.14	29
			44.70	84.90	40.20	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	
			84.90	86.30	1.40	4140	12	212	10	287	0.7	100	851	6.92	17
			86.30	327.00	240.70	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	
		16.6 - 17.2 FRACTURE ZONE, no min;													
		21.8 FRACTURE, NO MIN;													
		43.2 - 44.7 < 5% disse fine and some coarse py;													
		160.5 - 164 FRACTURE ZONE;													
		165 - 166 FRACTURE ZONE;													
		204 - 216.4 andesitic, fine grained, weakly foliated, trc of disse py (< 1%);													
		240.5 - 241.5 mafic dyke;													
		255.4 SHEAR;													
		270 - 271 blocky;													
327		(END OF HOLE)													

HOLE No: BT05

CHAMPION BEAR RESOURCES LTD.

DIAMOND DRILL LOG

PROPERTY: BearTrack Lake
 HOLE No.: B706
 Collar Eastings: -475.00
 Collar Northings: 135.00
 Collar Elevation: 0.00
 Grid: BearTrack

Collar Inclination: -45.00
 Grid Bearing: 231.00
 Final Depth: 355.00 feet

Logged by: H. Petak
 Date:
 Down-hole Survey:

FROM	TO	LITHOLOGICAL DESCRIPTION	FROM	TO	WIDTH	ASSAYS														
						Sample	Au(ppb)	Cu(ppm)	Pb(ppm)	Zn(ppm)	Ag(ppm)	Ni(ppm)	Mn(ppm)	Fe(%)	As(ppm)					
0	B	(CASING)																		
8	196	(DIORITE)	0.00	23.80	23.80	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		Dark grey, med to coarse-grained, hbl, fldsp, some chl (after hbl ?), little or no qtz, massive to mod foliated (avg 45 deg to ca);	23.80	24.30	0.50	4141	23	336	13	172	1.0	149	828	5.86	25					
			24.30	48.30	24.00	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
			48.30	52.00	3.70	4142	16	134	55	103	0.6	95	612	5.73	10					
			52.00	96.90	44.90	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		8 - 15.7 blocky;	96.90	98.20	1.30	4143	265	883	16	287	1.9	90	596	6.31	187					
		24.5 - 25 mafic dyke with 5% py at upper contact;	98.20	142.00	43.80	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		48.3 - 52.2 3 - 5% dissen py;	142.00	147.20	5.20	4144	374	330	32	1208	1.3	170	772	9.86	345					
		68.5 - 7.5 mafic dyke with trc of dissen py (< 1%);																		
		97.4 - 98 qtz with semi-massive py;																		
		107 - 110.5 mafic dyke;																		
		114.3 3" qtz vein;																		
		120 2" qtz vein;																		
		141 - 147 fine-grained mafic rock (mafic dyke ?) with dissen py incl 2 massive bands about 1" wide at 143 (assoc with qtz) and at 145.6 resp.																		
196	211	(ANDESITE)																		
		Dark greenish grey, fine-grained, massive to poorly fol;																		
211	238.5	(DIORITE)																		
		Same as higher up in the section except mostly medium grained;																		
238.5	268	(DACITE)																		
		Light greenish-grey, fine-grained, massive; evidence of strong fracturing, fractures healed;																		
268	355	(ANDESITE) with tuffaceous portions	147.20	295.10	147.90	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		Dark greenish grey, fine-grained, massive to mod foliated (15 - 20 deg to ca); hbl, fldsp, some chl (after hbl ?), little or no qtz; occas trc of py; some carb and qtz veining (fracture fillings);	295.10	295.30	0.20	4145	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
			295.30	355.00	59.70	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		295.3 0.5" carb vein with 50% sphal (?);																		
		301.6 - 304.3 qtz vein, fract and sheared, no min;																		
		306.6 - 307.3 qtz vein, same as above;																		
		321 5" qtz vein;																		

CHAMPION BEAR RESOURCES LTD.

DIAMOND DRILL LOG

PROPERTY: BearTrack Lake
 HOLE No.: BTO6

Page 2

FROM	TO	LITHOLOGICAL DESCRIPTION	FROM	TO	WIDTH	Sample	ASSAYS							
							Au(ppb)	Cu(ppa)	Pb(ppa)	Zn(ppa)	Ag(ppa)	Ni(ppa)	Mn(ppa)	Fe(%)
350	355	fragmental (flow brecc ?), trc of fine py;												
355		(END OF HOLE)												

HOLE No: BTO6

CHAMPION BEAR RESOURCES LTD.

DIAMOND DRILL LOG

PROPERTY: BearTrack Lake
 HOLE No.: BTO6
 Collar Eastings: -475.00
 Collar Northings: 135.00
 Collar Elevation: 0.00
 Grid: BearTrack

Collar Inclination: -45.00
 Grid Bearing: 231.00
 Final Depth: 355.00 feet

Logged by: H. Petak
 Date:
 Down-hole Survey:

FROM	TO	LITHOLOGICAL DESCRIPTION	FROM	TO	WIDTH	ASSAYS												
						Sample	Au(ppb)	Cu(ppm)	Pb(ppm)	Zn(ppm)	Ag(ppm)	Ni(ppm)	Mn(ppm)	Fe(%)	As(ppm)			
0	8	(CASING)																
8	196	(DIORITE)	0.00	23.80	23.80	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		Dark grey, med to coarse-grained, hbl, fldsp, some chi	23.80	24.30	0.50	4141	23	336	13	172	1.0	149	828	5.86	25			
		(after hbl ?), little or no qtz, massive to mod foliated	24.30	48.30	24.00	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		(avg 45 deg to ca);	48.30	52.00	3.70	4142	16	134	55	103	0.6	95	612	5.73	10			
		8 - 15.7 blocky;	52.00	96.90	44.90	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		24.5 - 25 mafic dyke with 5% py at upper contact;	96.90	98.20	1.30	4143	265	883	16	287	1.9	90	596	6.31	187			
		48.3 - 52.2 3 - 5% disse py;	98.20	142.00	43.80	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		68.5 - 7.5 mafic dyke with trc of disse py (< 12);	142.00	147.20	5.20	4144	374	330	32	1208	1.3	170	772	9.86	345			
		97.4 - 98 qtz with semi-massive py;																
		107 - 110.5 mafic dyke;																
		114.3 3" qtz vein;																
		120 2" qtz vein;																
		141 - 147 fine-grained mafic rock (mafic dyke ?) with																
		disse py incl 2 massive bands about 1" wide																
		at 143 (assoc with qtz) and at 145.6 resp.																
196	211	(ANDESITE)																
		Dark greenish grey, fine-grained, massive to poorly fol;																
211	238.5	(DIORITE)																
		Same as higher up in the section except mostly medium																
		grained;																
238.5	268	(DACITE)																
		Light greenish-grey, fine-grained, massive; evidence of																
		strong fracturing, fractures healed;																
268	355	(ANDESITE) with tuffaceous portions	147.20	295.10	147.90	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		Dark greenish grey, fine-grained, massive to mod foliated	295.10	295.30	0.20	4145	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		(15 - 20 deg to ca); hbl, fldsp, some chi (after hbl ?),	295.30	355.00	59.70	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		little or no qtz; occas trc of py; some carb and qtz																
		veining (fracture fillings);																
		295.3 0.5" carb vein with 50% sphal (?);																
		301.6 - 304.3 qtz vein, fract and sheared, no min;																
		306.6 - 307.3 qtz vein, same as above;																
		321 5" qtz vein;																

CHAMPION BEAR RESOURCES LTD.

DIAMOND DRILL LOG

PROPERTY: BearTrack Lake
 HOLE No.: B706

Page 2

FROM	TO	LITHOLOGICAL DESCRIPTION	FROM	TO	WIDTH	Sample	ASSAYS												
							Au(ppb)	Cu(ppm)	Pb(ppm)	Zn(ppm)	Ag(ppm)	Ni(ppm)	Mn(ppm)	Fe(%)	As(ppm)				
	350	355																	
	355.	(END OF HOLE)																	

HOLE No: B706

CHAMPION BEAR RESOURCES LTD.

DIAMOND DRILL LOG

PROPERTY: BearTrack Lake
 HOLE No.: BT07
 Collar Eastings: -200.00
 Collar Northings: 125.00
 Collar Elevation: 0.00
 Grid: BearTrack

Collar Inclination: -45.00
 Grid Bearing: 231.00
 Final Depth: 396.00 feet

Logged by: H. Petak
 Date:
 Down-hole Surveys:

FROM	TO	LITHOLOGICAL DESCRIPTION	ASSAYS												
			FROM	TO	WIDTH	Sample	Au(ppb)	Cu(ppm)	Pb(ppm)	Zn(ppm)	Ag(ppm)	Ni(ppm)	Mn(ppm)	Fe(%)	As(ppm)
0	12	(CASING)													
12	82	(DIORITE) Dark greenish-grey, fine- to medium-grained, well foliated at 40 - 45 deg to ca; fids, hbl, some chl (after hbl ?); some aplitic and carbonate veining partic towards the lower part of the section;													
12	15	very blocky;													
17		strongly weathered fracture;													
31	32	fracturing, very blocky;													
82	108	(BRECCIA) Flow Breccia ? Fine-grained andesitic matrix with felsic (feldsp) fragmts up to several cm long, stretched with long axis parall to plane of foliation; fragmts subangular; top and bottom contact of section gradational;													
108	396	(ANDESITE) Greenish-grey, fine-grained, massive to weakly foliated at 45 deg to ca; sporadic trc of py;	0.00	168.00	168.00	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	
		110 - 112 fine disse py, < 1%;	168.00	170.50	2.50	4146	16	129	4	110	TRACE	52	746	4.41	30
		115.5 1" qtz vein, no min;	170.50	178.30	7.80	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		136 - 138 fine disse py, < 1%;	178.30	180.20	1.90	4147	25	60	TRACE	94	TRACE	43	1050	3.63	TRACE
		158 3" qtz vein, no min, some turn at lower contact;	180.20	187.60	7.40	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		168 - 169 qtz filled shear with some py (up to 5%, avg 3%), py partially in fract, also chl and turn;	187.60	188.50	0.90	4148	14	80	3	106	0.3	100	860	5.21	10
		178.8 3" qtz vein, disse py on both sides, up to 10% py at 180;	188.50	210.50	22.00	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		187.6 - 188.5 5 - 10% fine disse py;	210.50	211.50	1.00	4149	9	99	TRACE	51	0.2	36	694	2.94	4
		196 - 197.4 1% fine disse py;		211.50	396.00	184.50	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		200 1" qtz vein;													
		235 - 235.5 qtz vein, trc op py;													
		241 1" py up to 5%;													
		280 - 286.6 qtz vein;													
396.		(END OF HOLE)													

CHAMPION BEAR RESOURCES LTD.

DIAMOND DRILL LOG

PROPERTY: BearTrack Lake
 HOLE No.: BTOB
 Collar Eastings: -839.00
 Collar Northings: 58.00
 Collar Elevation: 0.00
 Grid: BearTrack

Collar Inclination: -45.00
 Grid Bearing: 150.00
 Final Depth: 166.00 feet

Logged by: H. Petak
 Date:
 Down-hole Survey:

FROM	TO	LITHOLOGICAL DESCRIPTION	FROM	TO	WIDTH	Sample	ASSAYS										
							Au(ppb)	Cu(ppa)	Pb(ppa)	Zn(ppa)	Ag(ppa)	Ni(ppa)	Mn(ppa)	Fe(%)	As(ppa)		
0	34	(CASING)															
34	145.6	(DIORITE) Dark grey to dark greenish-grey, mostly coarse-grained with occas fine-grained portions, mostly massive to poorly foliated (generally the coarse-gr port) with some short nod foliated (usually fine-gr) sections; fol avg at 45 deg to ca; hbl, fldsp, occas chl (after hbl ?), little to no qtz; occas trc of py; some minor qtz and carb veining;	0.00 46.00	46.00 53.60	46.00 7.60	N.S. 4150	N.S. 733	N.S. NIL	N.S. NIL	N.S. NIL	N.S. NIL	N.S. NIL	N.S. NIL	N.S. NIL	N.S. NIL	N.S. NIL	N.S. NIL
46	53.6	SULFIDE ZONE: heavy dissen to massive py; apart from a 3" qtz vein (with turu) at 46.7, the entire section shows some silicification.															
55.4 - 55.8		qtz vein with chl and little turu;															
76.3 - 77.9		mafic dyke;															
112.3 - 114		mafic dyke;															
116.3 - 117.4		mafic dyke with 2" qtz vein in center;															
122.4 - 127.6		mafic dyke;															
145.6	166	(ANDESITE) Dark greenish-grey, fine-grained, massive to poorly fol, hbl, chl, little fldsp and qtz, local trc of py;	53.60	166.00	112.40	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
166.		(END OF HOLE)															

CHAMPION BEAR RESOURCES LTD.

DIAMOND DRILL LOG

PROPERTY: BearTrack Lake
 HOLE No.: BT09
 Collar Eastings: -739.00
 Collar Northings: 60.00
 Collar Elevation: 0.00
 Grid: BearTrack

Collar Inclination: -55.00
 Grid Bearing: 231.00
 Final Depth: 126.00 feet

Logged by: H. Petak
 Date:
 Down-hole Survey:

FROM	TO	LITHOLOGICAL DESCRIPTION	FROM	TO	WIDTH	ASSAYS											
						Sample	Au(ppb)	Cu(ppm)	Pb(ppm)	Zn(ppm)	Ag(ppm)	Ni(ppm)	Mn(ppm)	Fe(%)	As(ppm)		
0	4	(CASING)															
4	126	(DIORITE)	0.00	5.00	5.00	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		Dark greenish-grey to grey, mostly coarse-gr, occas fine-	5.00	6.50	1.50	4151	25	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		to medium-grained, generally massive to poorly foliated,	6.50	23.00	16.50	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		rarely mod foliated at 35 - 45 deg to ca; hbl, fids, occas	23.00	23.50	0.50	4152	27	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		chl (after hbl ?), very little or no qtz; occas irc of py;	23.50	26.00	2.50	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
			26.00	27.00	1.00	4153	8515	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
			27.00	126.00	99.00	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
		5 - 6.5 < 31 disse py;															
		8 - 9 qtz vein;															
		12 - 3" disse py, 12;															
		23 - 23.5 31 disse py along fol;															
		26 - 27 heavy disse to semi-massive py in siliceous,															
		well foliated rock; possible shear zone;															
		31 - 32 shear zone, chl, no min;															
		48 - 53 silicification; shear at 51.5;															
		78 - 85 chloritization with pegmat veining;															
		99 - 1" pegmat with tour;															
126		(END OF HOLE)															

CHAMPION BEAR RESOURCES LTD.

DIAMOND DRILL LOG


PROPERTY: BearTrack Lake
 HOLE No.: BT10
 Collar Eastings: -850.00
 Collar Northings: 55.00
 Collar Elevation: 0.00
 Grid: Beartrack

Collar Inclination: -45.00
 Grid Bearing: 231.00
 Final Depth: 125.00 feet

Logged by: H. Petak
 Date:
 Down-hole Survey:

FROM	TO	LITHOLOGICAL DESCRIPTION	FROM	TO	WIDTH	ASSAYS											
						Sample	Au(ppb)	Cu(ppm)	Pb(ppm)	Zn(ppm)	Ag(ppm)	Ni(ppm)	Mn(ppm)	Fe(%)	As(ppm)		
0	25	(CASING)															
25	104	(DIORITE) Dark greenish-grey, medium- to coarse-grained, massive to poorly foliated (at 45 to 50 deg to ca); Abi, fldsp, chl (after hbl ?), little or no Qtz, occas fine dissea mgt; some occas thin Qtz and carb veining;															
	35	- 37 mafic dyke;															
	85	- 86.5 mafic dyke;															
	102	shear, no min;															
104	125	(ANDESITE) Dark green to greyish green, usually fine-grained, poorly to mod foliated; chl, hbl, minor fldsp; some very fine Qtz and carb veining;	0.00	125.00	125.00	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.
	125	(END OF HOLE)															

K 1161174



K 1133507

BT11

142 50 m

195 m

K 1161179

4900

133508

CHAMPION BEAR RESOURCES LTD.

DIAMOND DRILL LOG

PROPERTY: BearTrack Lake
 HOLE No.: BT11
 Collar Eastings: -1200.00
 Collar Northings: -625.00
 Collar Elevation: 0.00
 Grid: BearTrack

Collar Inclination: -45.00
 Grid Bearing: 180.00
 Final Depth: 406.00 feet

Logged by: H. Petak
 Date:
 Down-hole Survey:

FROM	TO	LITHOLOGICAL DESCRIPTION	FROM	TO	WIDTH	ASSAYS													
						Sa(ppb)	Au(ppb)	Cu(ppm)	Pb(ppm)	Zn(ppm)	Ag(ppm)	Ni(ppm)	Mn(ppm)	Fe(%)	As(ppm)				
0	46	(CASING)																	
28	46	5 ft of very blocky core recovered; DIORITE ?																	
46	174	(DIORITE)	0.00	61.50	61.50	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	
		Greenish grey to dark grey, mostly fine- to medium-grained, locally coarse-grained, generally well foliated to thinly laminated at 30 to 45 deg to ca;	61.50	65.50	4.00	4154	TRACE	73	4	39	TRACE	130	742	4.43	7				
		hbl, fldsp, chl (after hbl ?), little or no qtz; long parts of the section carry up to 5% and occas more	65.50	96.80	31.30	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	
		extremely fine disse py and mgt;	96.80	100.40	3.60	4155	TRACE	70	3	127	0.4	163	743	4.93	34				
		qtz and carb veining is fairly common and occas associated with an increase in the amt of sulfides.	100.40	112.50	12.10	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	
			112.50	115.00	2.50	4156	TRACE	80	4	73	0.5	115	724	4.45	34				
			115.00	152.00	37.00	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	
			152.00	156.70	4.70	4157	TRACE	76	2	37	0.5	91	310	3.44	26				
			156.70	166.70	10.00	4158	TRACE	85	3	112	0.4	153	969	4.82	35				
			166.70	174.00	7.30	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	
130	-	narrow shear and fracture zone sub-parallel to ca;																	
142	148	mafic and mostly elongated fragments in a very fine-grained mafic matrix; fragment size averaged few mm and ranges up to 1 cm in length; (flow top brecc ?); fragmentation;																	
161		fragmentation;																	
174	233	(ANDESITE) buffaceous	174.00	189.00	15.00	4159	TRACE	81	5	105	0.5	143	910	4.59	34				
		Dark greenish-grey, very fine-grained, mostly massive, in places vaguely banded (at 45 deg to ca); varying amts of disse py occur through most of the section; locally accomp by very fine disse mgt;	189.00	194.00	5.00	4160	6	64	2	56	0.6	94	1000	4.21	39				
			194.00	199.00	5.00	4161	TRACE	58	5	71	0.4	112	1030	4.00	25				
			199.00	206.00	7.00	4162	TRACE	79	4	75	0.3	185	758	5.74	28				
			206.00	216.00	10.00	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	
			216.00	226.00	10.00	4163	TRACE	76	2	85	0.4	152	753	4.54	23				
189.5	- 188.5	heavy disse and thin laminae of py (10 - 20% of py);																	
199	- 199.5	thin bands of semi-massive py (40% py);																	
216	- 233	SULFIDE ZONE (30 - 40% py) assoc with strong qtz and carb veining; also some mgt;																	
233	406	(ANDESITIC TUFF), locally dacitic ?	226.00	233.30	7.30	4164	TRACE	96	3	171	0.3	113	940	4.63	23				
		Dark grey, fine-grained, well foliated to thinly laminated; hbl, fldsp, chl, locally some qtz;	233.30	304.60	71.30	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	
		most of the section contains very fine disse py (avg 1% loc up to 3% py) and locally some mgt;	304.60	307.10	2.50	4165	TRACE	83	7	87	0.2	164	688	5.08	31				
		thin qtz and carb veinlets are common throughout most of the section.	307.10	395.30	88.20	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	
			395.30	396.00	0.70	4166	6	75	10	76	0.3	170	825	6.17	36				
			396.00	406.00	10.00	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	N.S.	

CHAMPION BEAR RESOURCES LTD.

DIAMOND DRILL LOG

PROPERTY: BearTrack Lake
HOLE No.: BT11

Page 2

ASSAYS

FROM	TO	LITHOLOGICAL DESCRIPTION	FROM	TO	WIDTH	Sample	Au(ppb)	Cu(ppm)	Pb(ppm)	Zn(ppm)	Ag(ppm)	Ni(ppm)	Mn(ppm)	Fe(X)	As(ppm)	
306		2" qtz vein in shear zone with assoc py (SX py);														
316.5	- 324	STRONG FRACTURE ZONE, mostly sub-parallel to ca; fract are often carbonate filled and py coated; also some act on fract planes;														
324	- 327.7	porphyritic dyke pinkish, med- to coarse-grained with 2 - 4 mm fidsp porphyroclasts; both contacts are very sharp.														
331.8	- 333.6	porphyritic dyke, same as above except finer grained;														
343		0.5 ft fracture zone, no min;														
365		fracture plane with heavy py coating;														
372	- 386	porphyritic dyke, same as above														
406		(END OF HOLE)														

HOLE No: BT11



BARRINGER LABORATORIES

BARRINGER / ACCURASSAY LABORATORIES
THUNDER BAY DIVISION

5735 McADAM ROAD
MISSISSAUGA, ONTARIO
CANADA L4Z 1N9
PHONE: (416) 890-8566
FAX: (416) 890-8575

4-Mar-92

INDEPENDENT EXPLORATION SERVICES LTD.
P.O. Box 7, Station A
Winnipeg, MB
R3K 1Z9

Page: 1
Copy: 1 of 1
Set: 1

Attn: Mr. Lou Chastko
Project: Beartrack

Received: 3-Mar-92 07:45

PO #:

Job: 921019R

Status: Preliminary

Core Samples

Sample	AU	AU
	FA/AA3 ppb	FA/AA3 oz/T
4101	15	<0.001
4102	29	<0.001
4103	11	<0.001
4104	41	0.001
4105	177	0.005
4106	7	<0.001
4107	21	<0.001
4108	11	<0.001
4109	13	<0.001
4110	<5	<0.001
4111	69	0.002
4112	<5	<0.001
4113	<5	<0.001
4114	<5	<0.001
4115	213	0.006
4116	203	0.006
4117	46	0.001
4118	29	<0.001
4119	<5	<0.001
4120	124	0.004

SERVICES FOR THE EARTH AND ENVIRONMENTAL SCIENCES



BARRINGER LABORATORIES

BARRINGER / ACCURASSAY LABORATORIES
THUNDER BAY DIVISION

5735 McADAM ROAD
MISSISSAUGA, ONTARIO
CANADA L4Z 1N9
PHONE: (416) 890-8588
FAX: (416) 890-8578

12-Mar-92

INDEPENDENT EXPLORATION SERVICES LTD.
P.O. Box 7, Station A
Winnipeg, MB
R3K 1Z9

Page: 2
Copy: 1 of 1
Set: 2

Attn: Mr. Lou Chastko
Project: Beartrack

PO #:

Received: 3-Mar-92 07:45

Job: 921019R

Status: Final

Core Samples

Sample	Mo ICAP PPM	Cu ICAP PPM	Pb ICAP PPM	Zn ICAP PPM	Ag ICAP PPM	Ni ICAP PPM	Co ICAP PPM
4101	3	24	17	58	0.1	71	56
4102	1	86	9	46	<0.1	108	34
4103	1	9	14	63	<0.1	74	29
4104	2	19	14	152	0.6	78	31
4105	2	75	14	62	2.1	153	67
4106	2	19	8	69	<0.1	65	30
4107	2	117	21	137	0.5	76	50
4108	2	43	7	88	0.3	106	60
4109	2	38	8	249	0.1	76	42
4110	3	49	12	170	0.7	57	41
4111	3	57	10	216	<0.1	73	135
4112	3	37	11	23	<0.1	50	36
4113	3	30	14	37	<0.1	63	42
4114	2	17	16	91	<0.1	85	29
4115	2	111	34	193	<0.1	83	44
4116	3	95	11	188	0.1	33	42
4117	2	314	10	405	0.3	112	42
4118	3	63	11	165	0.1	80	38
4119	3	21	16	128	<0.1	33	40
4120	3	347	18	122	0.4	85	122

Sample	Mn ICAP PPM	Fe ICAP %	As ICAP PPM	Sb ICAP PPM	Bi ICAP PPM
4101	776	5.00	37	<2	4
4102	411	4.32	19	<2	<3
4103	512	3.23	13	<2	5
4104	867	3.16	20	<2	3

SERVICES FOR THE EARTH AND ENVIRONMENTAL SCIENCES



6735 McADAM ROAD
 MISSISSAUGA, ONTARIO
 CANADA L4Z 1N9
 PHONE: (416) 890-8568
 FAX: (416) 890-8575

BARRINGER / ACCURASSAY LABORATORIES
 THUNDER BAY DIVISION

12-Mar-92

INDEPENDENT EXPLORATION SERVICES LTD.
 P.O. Box 7, Station A
 Winnipeg, MB
 R3K 1Z9

Page: 3
 Copy: 1 of 1
 Set: 2

Attn: Mr. Lou Chastko
 Project: Beartrack

Received: 3-Mar-92 07:45

PO #:

Job: 921019R

Status: Final

Core Samples

Sample	Mn ICAP PPM	Fe ICAP %	As ICAP PPM	Sb ICAP PPM	Bi ICAP PPM
4105	759	5.86	125	<2	<3
4106	708	3.50	20	5	<3
4107	620	7.41	32	4	<3
4108	625	5.12	39	<2	<3
4109	729	2.94	21	<2	<3
4110	753	6.98	18	4	<3
4111	805	6.17	114	6	<3
4112	573	1.68	8	<2	7
4113	321	2.29	16	3	<3
4114	936	3.51	3	<2	<3
4115	1260	6.52	166	<2	<3
4116	461	5.09	64	<2	<3
4117	633	6.13	75	2	<3
4118	795	5.44	28	<2	<3
4119	641	4.83	18	<2	<3
4120	1520	8.86	160	<2	<3



BARRINGER LABORATORIES

BARRINGER / ACCURASSAY LABORATORIES
THUNDER BAY DIVISION

5735 MCADAM ROAD
MISSISSAUGA, ONTARIO
CANADA L4Z 1N9
PHONE: (416) 890-8566
FAX: (416) 890-8575

12-Mar-92

INDEPENDENT EXPLORATION SERVICES LTD.
P.O. Box 7, Station A
Winnipeg, MB
R3K 1Z9

Page: 4
Copy: 1 of 1
Set: 2

Attn: Mr. Lou Chastko
Project: Beartrack

Received: 3-Mar-92 07:45

PO #:

Job: 921019R

Status: Final

Signed:

Howard Lahti
.....
Howard Lahti, Ph.D.
Laboratory Manager

SERVICES FOR THE EARTH AND ENVIRONMENTAL SCIENCES



BARRINGER LABORATORIES

BARRINGER / ACCURASSAY LABORATORIES
THUNDER BAY DIVISION

5735 McADAM ROAD
MISSISSAUGA, ONTARIO
CANADA L4Z 1N9
PHONE: (416) 890-8566
FAX: (416) 890-8575

25-Mar-92

INDEPENDENT EXPLORATION SERVICES LTD.
P.O. Box 7, Station A
Winnipeg, MB
R3K 1Z9

Page: 1
Copy: 1 of 1
Set: 1

Attn: Mr. Lou Chastko
Project: Bear Track

PO #:

Received: 5-Mar-92 09:27

Job: 921021R

Status: Final

Core Samples

Sample	Au	Au
	FA/AA3 ppb	FA/AA3 oz/T
4121	18	<0.001
4122	391	0.011
4123	7	<0.001
4124	7	<0.001
4125	5	<0.001
4126	5	<0.001
4127	14	<0.001
4128	<5	<0.001
4129	<5	<0.001
4130	<5	<0.001
4131	23	<0.001
4132	144	0.004
4133	287	0.008
4134	12	<0.001
4135	5	<0.001
4136	7	<0.001
4137	<5	<0.001
4138	5	<0.001



BARRINGER LABORATORIES

BARRINGER / ACCURASSAY LABORATORIES
THUNDER BAY DIVISION

5735 McADAM ROAD
MISSISSAUGA, ONTARIO
CANADA L4Z 1N9
PHONE: (416) 890-8566
FAX: (416) 890-8575

25-Mar-92

INDEPENDENT EXPLORATION SERVICES LTD.
P.O. Box 7, Station A
Winnipeg, MB
R3K 1Z9

Page: 2
Copy: 1 of 1
Set: 2

Attn: Mr. Lou Chastko
Project: Bear Track

Received: 5-Mar-92 09:27

PO #:

Job: 921021R

Status: Final

Core Samples

Sample	Mo ICAP ppm	Cu ICAP ppm	Pb ICAP ppm	Zn ICAP ppm	Ag ICAP ppm	Ni ICAP ppm	Co ICAP ppm
4121	2	280	6	312	0.1	101	40
4122	1	198	17	662	0.4	127	59
4123	1	104	8	134	<0.1	88	40
4124	1	128	9	109	0.4	95	48
4125	1	111	8	109	0.5	99	48
4126	1	67	10	121	0.2	86	49
4127	1	74	8	166	0.4	94	52
4128	2	68	15	95	<0.1	68	41
4129	1	54	7	110	<0.1	74	31
4130	<1	43	<2	99	<0.1	111	30
4131	1	108	4	245	0.2	95	39
4132	2	1116	4	813	0.7	136	32
4133	3	177	476	1688	3.3	168	57
4134	<1	77	9	135	0.2	137	40
4135	1	38	<2	76	<0.1	106	31
4136	2	178	8	80	0.6	96	45
4137	1	81	6	88	0.4	101	44
4138	2	135	2	128	0.3	107	46

Sample	Mn ICAP ppm	Fe ICAP %	As ICAP ppm	Sb ICAP ppm	Bi ICAP ppm
4121	789	7.16	15	5	<3
4122	830	6.77	84	7	6
4123	811	4.38	17	7	<3
4124	800	5.02	22	4	<3
4125	811	5.21	14	8	<3
4126	831	4.49	15	7	3



BARRINGER / ACCURASSAY LABORATORIES
THUNDER BAY DIVISION

5735 McADAM ROAD
MISSISSAUGA, ONTARIO
CANADA L4Z 1N9
PHONE: (416) 890-8566
FAX: (416) 890-8575

25-Mar-92

INDEPENDENT EXPLORATION SERVICES LTD.
P.O. Box 7, Station A
Winnipeg, MB
R3K 1Z9

Page: 3
Copy: 1 of 1
Set: 2

Attn: Mr. Lou Chastko
Project: Bear Track

Received: 5-Mar-92 09:27

PO #:

Job: 921021R

Status: Final

Core Samples

Sample	Mn ICAP ppm	Fe ICAP %	As ICAP ppm	Sb ICAP ppm	Bi ICAP ppm
4127	882	5.00	23	2	<3
4128	625	5.09	13	5	<3
4129	585	3.00	3	7	<3
4130	746	3.75	<2	3	<3
4131	647	4.52	26	10	3
4132	970	7.97	20	11	<3
4133	623	7.74	170	18	.11
4134	798	4.73	10	4	<3
4135	840	3.72	<2	3	<3
4136	707	5.08	13	12	<3
4137	793	4.77	9	9	<3
4138	762	5.34	13	7	<3



BARRINGER / ACCURASSAY LABORATORIES
THUNDER BAY DIVISION

5735 McADAM ROAD
MISSISSAUGA, ONTARIO
CANADA L4Z 1N9
PHONE: (416) 890-8566
FAX: (416) 890-8575

25-Mar-92

INDEPENDENT EXPLORATION SERVICES LTD.
P.O. Box 7, Station A
Winnipeg, MB
R3K 1Z9

Page: 4
Copy: 1 of 1
Set : 2


Attn: Mr. Lou Chastko
Project: Bear Track

Received: 5-Mar-92 09:27

PO #:

Job: 921021R Status: Final

Signed:


.....
Jeffrey Davis B.Sc.
Supervisor Environmental Services



BARRINGER LABORATORIES

BARRINGER / ACCURASSAY LABORATORIES
THUNDER BAY DIVISION

5735 McADAM ROAD
MISSISSAUGA, ONTARIO
CANADA L4Z 1N9
PHONE: (416) 890-8566
FAX: (416) 890-8575

25-Mar-92

INDEPENDENT EXPLORATION SERVICES LTD.
P.O. Box 7, Station A
Winnipeg, MB
R3K 1Z9

Page: 1
Copy: 1 of 1
Set: 1

Attn: Mr. Lou Chastko
Project: Bear Track

PO #:

Received: 10-Mar-92 08:01

Job: 921023R Status: Final

Core Samples

Sample	Au FA/AA3 ppb	Au FA/AA3 oz/T
4139	12	<0.001
4140	12	<0.001
4141	23	<0.001
4142	16	<0.001
4143	265	0.008
4144	374	0.011
4146	16	<0.001
4147	25	<0.001
4148	14	<0.001
4149	9	<0.001



BARRINGER LABORATORIES

BARRINGER / ACCURASSAY LABORATORIES
THUNDER BAY DIVISION

5735 McADAM ROAD
MISSISSAUGA, ONTARIO
CANADA L4Z 1N9
PHONE: (416) 890-8566
FAX: (416) 890-8575

25-Mar-92

INDEPENDENT EXPLORATION SERVICES LTD.
P.O. Box 7, Station A
Winnipeg, MB
R3K 1Z9

Page: 2
Copy: 1 of 1
Set: 2

Attn: Mr. Lou Chastko
Project: Bear Track

Received: 10-Mar-92 08:01

PO #:

Job: 921023R

Status: Final

Core Samples

Sample	Mo ICAP ppm	Cu ICAP ppm	Pb ICAP ppm	Zn ICAP ppm	Ag ICAP ppm	Ni ICAP ppm	Co ICAP ppm
4139	3	250	15	157	0.5	88	92
4140	2	212	10	287	0.7	100	47
4141	3	336	13	172	1.0	149	121
4142	2	134	55	103	0.6	95	49
4143	3	883	16	287	1.9	90	129
4144	2	330	32	1208	1.3	170	193
4146	3	129	4	110	<0.1	52	59
4147	5	60	<2	94	<0.1	43	39
4148	1	80	3	106	0.3	100	35
4149	5	99	<2	51	0.2	36	34

Sample	Mn ICAP ppm	Fe ICAP %	As ICAP ppm	Sb ICAP ppm	Bi ICAP ppm
4139	583	7.14	29	8	<3
4140	851	6.92	17	6	<3
4141	828	5.86	25	8	<3
4142	612	5.73	10	8	<3
4143	596	6.31	187	<2	9
4144	772	9.86	345	8	<3
4146	746	4.41	30	<2	<3
4147	1050	3.63	<2	<2	<3
4148	860	5.21	10	<2	<3
4149	694	2.94	4	<2	<3



BARRINGER LABORATORIES

BARRINGER / ACCURASSAY LABORATORIES
THUNDER BAY DIVISION

5735 McADAM ROAD
MISSISSAUGA, ONTARIO
CANADA L4Z 1N9
PHONE: (416) 890-8566
FAX: (416) 890-8575

25-Mar-92

INDEPENDENT EXPLORATION SERVICES LTD.
P.O. Box 7, Station A
Winnipeg, MB
R3K 1Z9

Page: 3
Copy: 1 of 1
Set: 2

Attn: Mr. Lou Chastko
Project: Bear Track


Received: 10-Mar-92 08:01

PO #:

Job: 921023R

Status: Final

Signed:


.....
Jeffrey Davis B.Sc.
Supervisor Environmental Services



BARRINGER LABORATORIES

BARRINGER / ACCURASSAY LABORATORIES
THUNDER BAY DIVISION

5735 McADAM ROAD
MISSISSAUGA, ONTARIO
CANADA L4Z 1N9
PHONE: (416) 890-8566
FAX: (416) 890-8575

30-Mar-92

INDEPENDENT EXPLORATION SERVICES LIMITED
P.O. Box 7, Station A
Winnipeg, MB
R3K 1Z9

Page: 1
Copy: 1 of 1
Set: 1

Attn: Mr. Lou Chastko
Project:

Received: 23-Mar-92 10:06

PO #:

Job: 924056T

Status: Final

Core Samples

Sample	Au FA/AA3 ppb	Au FA/AA3 oz/T	Mo ICAP ppm	Cu ICAP ppm	Pb ICAP ppm	Zn ICAP ppm	Ag ICAP ppm
4154	<5	<0.001	<1	73	4	39	<0.1
4155	<5	<0.001	1	70	3	127	0.4
4156	<5	<0.001	<1	80	4	73	0.5
4157	<5	<0.001	<1	76	2	37	0.5
4158	<5	<0.001	1	85	3	112	0.4
4159	<5	<0.001	1	81	5	105	0.5
4160	6	<0.001	<1	64	2	56	0.6
4161	<5	<0.001	1	58	5	71	0.4
4162	<5	<0.001	<1	79	4	75	0.3
4163	<5	<0.001	1	76	2	85	0.4
4164	<5	<0.001	2	96	3	171	0.3
4165	<5	<0.001	1	83	7	87	0.2
4166	6	<0.001	1	75	10	76	0.3

Sample	Ni ICAP ppm	Co ICAP ppm	Mn ICAP ppm	Fe ICAP %	As ICAP ppm	Sb ICAP ppm	Bi ICAP ppm
4154	130	40	742	4.43	7	2	<3
4155	163	43	743	4.93	34	4	<3
4156	115	44	724	4.45	34	5	<3
4157	91	41	310	3.44	26	2	<3
4158	153	48	969	4.82	35	5	<3
4159	143	46	910	4.59	34	5	<3
4160	94	34	1000	4.21	39	8	<3
4161	112	33	1030	4.00	25	2	<3
4162	185	45	758	5.74	28	3	<3
4163	152	17	753	4.54	23	2	<3
4164	113	34	940	4.63	23	2	<3



BARRINGER LABORATORIES

BARRINGER / ACCURASSAY LABORATORIES
THUNDER BAY DIVISION

5735 McADAM ROAD
MISSISSAUGA, ONTARIO
CANADA L4Z 1N9
PHONE: (416) 890-8566
FAX: (416) 890-8575

30-Mar-92

INDEPENDENT EXPLORATION SERVICES LIMITED
P.O. Box 7, Station A
Winnipeg, MB
R3K 1Z9

Page: 2
Copy: 1 of 1
Set: 1

Attn: Mr. Lou Chastko
Project:

Received: 23-Mar-92 10:06

PO #:

Job: 924056T

Status: Final

Core Samples

Sample	Ni ICAP ppm	Co ICAP ppm	Mn ICAP ppm	Fe ICAP %	As ICAP ppm	Sb ICAP ppm	Bi ICAP ppm
4165	164	50	688	5.08	31	2	<3
4166	170	43	825	6.17	36	2	<3



BARRINGER LABORATORIES

BARRINGER / ACCURASSAY LABORATORIES
THUNDER BAY DIVISION

5735 McADAM ROAD
MISSISSAUGA, ONTARIO
CANADA L4Z 1N9
PHONE: (416) 890-8566
FAX: (416) 890-8575

30-Mar-92

INDEPENDENT EXPLORATION SERVICES LIMITED
P.O. Box 7, Station A
Winnipeg, MB
R3K 1Z9

Page: 3
Copy: 1 of 1
Set: 1

Attn: Mr. Lou Chastko
Project:

Received: 23-Mar-92 10:06

PO #:

Job: 924056T

Status: Final

Signed:


.....
Jeffrey Davis, B.Sc., C.Chem.
Manager, Thunder Bay Division



5735 McADAM ROAD
MISSISSAUGA, ONTARIO
CANADA L4Z 1N9
PHONE: (416) 890-8566
FAX: (416) 890-8575

BARRINGER / ACCURASSAY LABORATORIES
THUNDER BAY DIVISION

8-Apr-92

INDEPENDENT EXPLORATION SERVICES LTD.
P.O. Box 7, Station A
Winnipeg, MB
R3K 1Z9

Page: 1
Copy: 1 of 1
Set: 1

Attn: Mr. Lou Chastko
Project: Bear Track

PO #:

Received: 13-Mar-92

Job: 921025R

Status: Final

Core Samples

Sample	Au FA/AA3 ppb	Au FA/AA3 oz/T
4150	733	0.021
4151	25	<0.001
4152	27	<0.001
4153	8515	0.248



5735 McADAM ROAD
MISSISSAUGA, ONTARIO
CANADA L4Z 1N9
PHONE: (416) 890-8566
FAX: (416) 890-8575

8-Apr-92

INDEPENDENT EXPLORATION SERVICES LTD.
P.O. Box 7, Station A
Winnipeg, MB
R3K 1Z9

Page: 2
Copy: 1 of 1
Set: 2

Attn: Mr. Lou Chastko
Project: Bear Track

Received: 13-Mar-92

PO #:

Job: 921025R

Status: Final

Core Samples

Sample	Mo ICAP ppm	Cu ICAP ppm	Pb ICAP ppm	Zn ICAP ppm	Ag ICAP ppm	Ni ICAP ppm	Co ICAP ppm
4150	5	359	23	1227	1.8	116	108
4151	2	157	13	505	0.1	132	49
4152	3	140	<2	220	0.4	191	59
4153	3	116	258	2615	2.1	198	56

Sample	Mn ICAP ppm	Fe ICAP %	As ICAP ppm	Sb ICAP ppm	Bi ICAP ppm
4150	409	10.69	276	5	<3
4151	980	9.50	24	4	<3
4152	912	6.55	49	3	<3
4153	508	9.26	342	13	<3



BARRINGER / ACCURASSAY LABORATORIES
THUNDER BAY DIVISION

5735 McADAM ROAD
MISSISSAUGA, ONTARIO
CANADA L4Z 1N9
PHONE: (416) 890-8566
FAX: (416) 890-8575

8-Apr-92

INDEPENDENT EXPLORATION SERVICES LTD.
P.O. Box 7, Station A
Winnipeg, MB
R3K 1Z9

Page: 3
Copy: 1 of 1
Set: 2

Attn: Mr. Lou Chastko
Project: Bear Track


Received: 13-Mar-92

PO #:

Job: 921025R

Status: Final

Signed:


.....
Jeffrey Davis, B.Sc., Chem.
Manager, Thunder Bay Division

Report of Work Conducted After Recording Claim

Transaction Number
W 9310 00035

Mining Act

Personal information collected on this form is obtained under the authority of the Mining Act. Its collection should be directed to the Provincial Manager, Mining Lands, Mining Division, Ontario, P3E 6A5, telephone (705) 670-7264.



900

- Instructions:**
- Please type or print and submit in duplicate.
 - Refer to the Mining Act and Regulations for requirements of mining assessment work or contact the Mining Recorder.
 - A separate copy of this form must be completed for each Work Group.
 - Technical reports and maps must accompany this form in duplicate.
 - A sketch, showing the claims the work is assigned to, must accompany this form.

Recorded Holder(s) Champion Bear Resources Ltd.		Client No. <i>116945</i>
Address 3805 - 7A Street S.W.; Calgary, Alberta; T2T 2Y8		Telephone No. 403-243-6997
Mining Division Kenora	Township/Area Laval TWP.	M or G Plan No. G-0823
Dates Work Performed From: January 1, 1992		To: March 31, 1992

Work Performed (Check One Work Group Only)

Work Group	Type
Geotechnical Survey	
Physical Work, Including Drilling	Diamond Drilling
Rehabilitation	
Other Authorized Work	
Assays	
Assignment from Reserve	

ONTARIO GEOLOGICAL SURVEY
GIS - ASSESSMENT FILES
APR 28 1993
RECEIVED

Total Assessment Work Claimed on the Attached Statement of Costs \$ ~~139,318.73~~ ~~101,194~~ 110,654. *h.c.*

Note: The Minister may reject for assessment work credit all or part of the assessment work submitted if the recorded holder cannot verify expenditures claimed in the statement of costs within 30 days of a request for verification.

Persons and Survey Company Who Performed the Work (Give Name and Address of Author of Report)

Name	Address
Wynne Mining Services Ltd.	Bissett, Manitoba
Independent Exploration Services Ltd.	104 Browning Blvd.; Winnipeg, Man. R3K 0L7

Attach a schedule if necessary)

Certification of Beneficial Interest * See Note No. 1 on reverse side

I certify that at the time the work was performed, the claims covered in this work report were recorded in the current holder's name or held under a beneficial interest by the current recorded holder.

Date: *March 11, 1993* Recorded Holder or Agent (Signature): *[Signature]*

Certification of Work Report



I certify that I have a personal knowledge of the facts set forth in this Work report, having performed the work or witnessed same during and/or after its completion and annexed report is true.

Name and Address of Person Certifying: *Louis C. Chastko, 104 Browning Blvd.; Winnipeg, Man.; R3K 0L7*

Telephone No.: *204-837-7641* Date: *March 11, 1993* Certified By (Signature): *[Signature]*

For Office Use Only



Total Value Cr. Recorded <i>5,110 654</i>	Date Recorded <i>MAR 16/93</i>	Mining Recorder <i>[Signature]</i>	Received Stamp KENORA Mining Div. RECEIVE D MAR 16 1993 7821011 12122486
	Deemed Approval Date <i>JUNE 14/93</i>	Date Approved <i>MAR 16/93</i>	
	Date Notice for Assessments Sent <i>MAR 24/93 (COMPLIANCE BY MAY 8/93)</i>		



800
600
400
200
0
AU (PPB)

CHAMPION BEAR RESOURCES LTD.
BEARTRACK LAKE PROPERTY
DIAMOND DRILL HOLE SECTION
SECTION **BT 1 & 2**
SCALE 1/250
INDEPENDENT EXPLORATION SERVICES LTD
DATE FEBRUARY, 1990





CHAMPION BEAR RESOURCES LTD.
 BEARTRACK LAKE PROPERTY
 DIAMOND DRILL HOLE SECTION
 SECTION - **BT 3**


SCALE: 1/200
 INDEPENDENT EXPLORATION SERVICES LTD.
 DATE: FEBRUARY, 1983



52F16SW8290 18 LAVAL

210

AU (PPB)





1600
1200
800
400
0
AU (PPB)

CHAMPION BEAR RESOURCES LTD.
BEARTRACK LAKE PROPERTY
DIAMOND DRILL HOLE SECTION
SECTION **BT 4**

SCALE 1/200
INDEPENDENT EXPLORATION SERVICES LTD.
DATE FEBRUARY, 1983



52F16SW8290 18 LAVAL




AU (PPB)

CHAMPION BEAR RESOURCES LTD.
 BEARTRACK LAKE PROPERTY
 DIAMOND DRILL HOLE SECTION
 SECTION **BT 5**

SCALE: 1/250
 INDEPENDENT EXPLORATION SERVICES LTD
 DATE: FEBRUARY, 1983



52F155W8290 18 LAVAL





1600
1200
800
400
0
AU (PPB)

CHAMPION BEAR RESOURCES LTD.
BEARTRACK LAKE PROPERTY
DIAMOND DRILL HOLE SECTION
SECTION 02 BT 6

SCALE 1/200
INDEPENDENT EXPLORATION SERVICES LTD.
DATE: FEBRUARY, 1989



52F16SW8290 18 LAVAL




CHAMPION BEAR RESOURCES LTD.
 BEARTRACK LAKE PROPERTY
 DIAMOND DRILL HOLE SECTION
 SECTION **BT 7**

SCALE: 1/250
INDEPENDENT EXPLORATION SERVICES LTD.
DATE: FEBRUARY, 1983



52F165W8290 18 LAVAL




1600
1200
800
400
0
AU (PPB)

CHAMPION BEAR RESOURCES LTD.
BEARTRACK LAKE PROPERTY
DIAMOND DRILL HOLE SECTION
SECTION BT 8 & 9

SCALE 1/800
DISPERSE EXPLORATION SERVICES LTD.
DATE FEBRUARY, 1993



52F16SW8290 18 LAVAL



1600
1200
800
400
0

AU (PPB)


CHAMPION BEAR RESOURCES LTD.
BEARTRACK LAKE PROPERTY
DIAMOND DRILL HOLE SECTION
SECTION CE BT 10

SCALE: 1/250
INDEPENDENT EXPLORATION SERVICES LTD.
DATE: FEBRUARY, 1982



52F16SW8290 18 LAVAL

270




1600
1200
800
400
0
AU (PPB)

CHAMPION BEAR RESOURCES LTD.
BEARTRACK LAKE PROPERTY
DIAMOND DRILL HOLE SECTION
SECTION (BT 11)

SCALE: 1/200
INDEPENDENT EXPLORATION SERVICES LTD.
DATE: FEBRUARY, 1988



52F16SW8290 18 LAVAL



CHAMPION BEAR RESOURCES LTD.
 DRYDEN PROJECT / NW-ONTARIO
 GRID: BEARTRACK LAKE (SW SHEET)
 GRID MAP

SURVEY DATE: WINTER 1991 / 92
 BY: INDEPENDENT EXPLORATION SERVICES LTD., WINNIPEG, MAN.

Scale 1:5000
 (metres)

